MSFC-HDBK-527 REV F

JSC 09604 REV F

SEPTEMBER 30, 1988

National Aeronautics and
Space Administration

George C. Marshall Space Flight Center
Marshall Space Flight Center, Alabama 35812

MATERIALS SELECTION LIST

FOR

SPACE HARDWARE SYSTEMS

MSFC - Form 464 (Rev. October 1976)

Information Handling Services, 2000

JSC 09604
Revision F
Effective Date:

November 15, 1986

MSFC-HDBK-527 12/29/88
Revision F
Effective Date:

November 15, 1986

MATERIALS SELECTION LIST

FOR

SPACE HARDWARE SYSTEMS

Submitted By:

C. F. Key 10-8-88

C. F. Key
Chief
Materials Selection & Control Office
Materials & Processes Laboratory

Approval:

R. J. Schwinghamer

R. J. Schwinghamer
Director
Materials & Processes Laboratory
Marshall Space Flight Center

Dr. L. Leger 11-30-88

Dr. L. Leger
Chief
Materials Technology Branch
Johnson Space Center

Carmelo J. Bianca Jr.

ED25

Information Handling Services, 2000

MSFC HDBK 527F

TABLE OF CONTENTS

PARAGRAPH	TITLE	PAGE NO.
1.0	SCOPE	1
1.1	ACCESSING & USE OF MAPTIS COMPUTERIZED DATA BASE	2
1.1.1	DATA SOURCES AND TEST NUMBER PREFIXES	3
1.1.2	MATERIAL RATINGS	3
1.2	METALLIC MATERIALS GENERAL	3
1.2.1	NICKEL PLATING	4
1.2.2	RATING CRITERIA	5
1.2.2.1	CORROSION RESISTANCE	5
1.2.2.2	STRESS CORROSION CRACKING SUSCEPTIBILITY	6
1.2.2.3	FLUID SYSTEM COMPATIBILITY - NITROGEN TETROXIDE (N_2O_4)	7
1.2.2.4	FLUID SYSTEM COMPATIBILITY - HYDRAZINE	7
1.2.2.5	COMPATIBILITY WITH LIQUID AND GASEOUS OXYGEN	8
1.2.2.6	TEST NO. 13 LIQUID AND GASEOUS OXYGEN MECHANICAL IMPACT	8
1.2.2.7	TEST NO. 14 GASEOUS OXYGEN PNEUMATIC IMPACT	8
1.2.2.8	FLUID SYSTEM COMPATIBILITY - LOW PRESSURE GASEOUS HYDROGEN (GH_2)	9
1.2.2.9	FLUID SYSTEM COMPATIBILITY - HIGH PRESSURE GASEOUS HYDROGEN (GH_2)	9
1.3	NONMETALLIC MATERIALS GENERAL	9
1.3.1	RATING CRITERIA AND SYMBOLS	10
1.3.2	FLAMMABILITY (FLAM)	10
1.3.2.1	GENERAL	10
1.3.2.1.1	WIRE AND CABLE	11
1.3.2.2	TOXICITY/OFFGASSING	11

Information Handling Services, 2000

PARAGRAPH	TITLE	PAGE NO.
1.3.2.3	ODOR	12
1.3.2.4	THERMAL VACUUM STABILITY (TVS)	12
1.3.2.5	STATIC AGE LIFE (AGE)	13
1.3.2.6	FLUID SYSTEM COMPATIBILITY - NITROGEN TETROXIDE	13
1.3.2.7	FLUID SYSTEM COMPATIBILITY - HYDRAULIC COMPATIBILITY	13
1.3.2.8	FLUID SYSTEM COMPATIBILITY - HYDRAZINE	14
1.3.2.9	COMPATIBILITY WITH LOX/GOX	14
1.3.2.10	TEST NO. 13 - LIQUID AND GASEOUS OXYGEN	14
1.3.2.11	TEST 14 - GASEOUS OXYGEN PNEUMATIC IMPACT TEST	15
1.4	STANDARD/COMMERCIAL PARTS	15
1.4.1	GENERAL	15
1.4.2	TABLE 3 CONTENT	15
1.4.3	RATING CODES FOR STANDARD/COMMERCIAL PARTS	16
1.5	FOREIGN ALLOY/CROSS REFERENCE	16
1.6	ATOMIC OXYGEN EFFECTS	17
1.7	TESTING	17
1.8	SAFETY	17
1.9	PAYLOAD BAY HARDWARE IN VENTED CONTAINERS	18
2.0	GROUND SUPPORT EQUIPMENT (GSE)	18
3.0	CONTROL OF MATERIALS OTHER THAN "A" RATED	18
4.0	IDENTIFICATION OF MATERIALS	18
5.0	EXPLANATION OF TERMS	18
6.0	ADDITIONAL INFORMATION	18

Information Handling Services, 2000

MSFC HDBK 527F

PARAGRAPH	TITLE	PAGE NO.
7.0	HANDBOOK SEARCH HINTS	19
8.0	ADDITION OF MATERIALS/STANDARD COMMERCIAL PARTS TO SELECTION LIST	20
9.0	ADDENDA/UPDATES	20
10.0	ACRONYMS	20
10.1	CURE INFORMATION	21
APPENDIX 1	MAPTIS USERS MANUAL	

Information Handling Services, 2000

MSFC HDBK 527F

FIGURES	NO.
MATERIAL USAGE AGREEMENT	1A
STRESS EVALUATION FORM	1B
CERTIFICATION MATERIAL USAGE AGREEMENT	1C
STANDARD/COMMERCIAL PARTS DATA INPUT SHEET	2
SELECTION LIST DATA SHEET, NONMETAL	3
SELECTION LIST DATA SHEET, METAL	4

Information Handling Services, 2000

TABLES	NO.
METALS	
METALS BY DESIGNATION WITH RATINGS	1A
METALS BY SPECIFICATION	1B
METALS BY CODE	1C
NONMETALS	
NONMETALS BY DESIGNATION WITH RATINGS	2A
NONMETALS BY SPECIFICATION	2B
NONMETALS BY CODE	2C
NONMETALS BY MANUFACTURER	2D
STANDARD/COMMERCIAL PARTS REPORT	3
FOREIGN ALLOY CROSS REFERENCE	
ALUMINUM	4A
STEEL	4B
TEST MATERIAL QUANTITY REQUIREMENTS	5

Information Handling Services, 2000

REFERENCES

Document Number	Document Title
NHB 8060.1B	Flammability, Odor, and Offgassing Requirements and Test Procedures for Materials in Environments that Support Combustion, with Errata
SP-R-0022A	Vacuum Stability Requirements of Polymeric Materials for Spacecraft Applications
SE-R-0006A	NASA-JSC Requirements for Materials & Processes
MSFC-SPEC-250A	Protective Finishes for Space Vehicles, Structures and Associated Flight Experiment
MSFC-SPEC-522B	Design Criteria for Controlling Stress Corrosion Cracking
JSC 11123	Space Transportation System Payload Safety Guidelines Handbook
NHB 1700.7A	Safety Policy and Requirements for Payload Using the Space Transportation System
50M02442	ATM Material Control for Contamination Due to Outgassing
MIL-H-83282	Hydraulic Fluid, Fire Resistant Synthetic Hydrogen Base, Aircraft
MSFC-STD-506C	Materials and Processes Control
SSP 30233B	Space Station Requirements for Materials and Processes
MIL-P-25732	Packing, Preformed, Petroleum Hydraulic Fluid Resistant, Limited Service at 275°F
QQ-N-290	Nickel Plating (Electrodeposited)
MIL-C-26074	Requirement for Coating, Electroless Nickel
MIL-STD-868	Nickel Plating, Low Embrittlement Electrodeposition

Information Handling Services, 2000

1.0 SCOPE

This document shall be used to obtain materials ratings for selection and reporting material usages to NASA in accordance with applicable Data Requirements specified in MSFC-STD-506, JSC SER-0006 and JSC 30233 or other contract requirements.

This document contains the NASA materials ratings for Flammability, Toxicity, Thermal Vacuum Stability, Age Life, Oxygen Compatibility, Fluid Compatibility, Stress Corrosion, Corrosion and a Foreign Alloy Cross Reference. However, the Design Agency is responsible to assure that all materials and processes used in the design and fabrication of space systems hardware shall be selected by considering the operational requirements for the particular application and the design engineering properties of the candidate materials.

The Materials listed in this document be used for all material selections in both the as-designed and as-built configurations. The suitability of a material is dependent on its specific application. Therefore, the ratings listed herein do not constitute acceptance or rejection of specific material applications. Additional rationale/test data, etc., may be required for some material applications. This additional information must be submitted in the manner specified in the contract.

If materials or Standard/Commercial Parts are used that are not listed in Tables 1, 2, or 3 of this document, the cognizant NASA materials and process organization must be contacted to determine procedures and information required for addition of an item to list. See 8.0 for additional information.

Table 1 lists metals by material designation with Material Code, Material Specification and/or Manufacturers. Materials are rated per NHB 8060.1B, MSFC-SPEC-522, MSFC-SPEC-250 as applicable for the following:

a. Corrosion (CORR)

b. Stress Corrosion Cracking (SCC)

c. Gaseous Oxygen Compatibility (GOX)

d. Liquid Oxygen Compatibility (LOX)

e. Nitrogen Tetroxide Compatibility (N_2O_4)

f. Hydrazine Compatibility (HDZE)

Information Handling Services, 2000

g. Low Pressure Hydrogen (LOH) < 450 psia

h. High Pressure Hydrogen (HIH) > 450 psia

Table 2 lists nonmetals by material designation. Also included are modified listings by specification and manufacturer. Materials are rated per NHB 8060.1 and/or SP-R-0022 as applicable for the following:

a. Flammability (FLAM)

b. Toxicity (TOX)

c. Thermal Vacuum Stability (TVS)

d. Liquid Oxygen (LOX)

e. High Pressure Gaseous Oxygen (HGOX) > 25 psia

f. Nitrogen Tetroxide Compatibility (N_2O_4)

g. Hydrazine Compatibility (HDZE)

h. Liquid Hydrogen (LH2)

i. Hydraulic Fluid Compatibility (HYD)

1.1 ACCESSING AND USE OF MAPTIS COMPUTERIZED DATA BASE

NOTE: The tables listed herein are part of the Materials and Processes Technical Information System (MAPTIS). Data on the Maptis System is available on floppy disks for IBM PCS. The ORACLE Data Base Mangement System must be obtained to use disk data. The use of MAPTIS System, allows string or phrase search. For example, if information regarding 'STYCAST 2850GT' is desired, the following search methology would yield required information.

'STYCAST' - You would find all designations that have STYCAST
'2850' - You would find all designations that have 2850
'2850GT' - You would find all designations that have 2850GT
'ADHESIVE' - You would find all adhesives

Detail procedures for accessing and searching MAPTIS are included in Appendix 1.

Note: Please contact C. F. Key FTS 824-2487 or commerical 205-544-2487 regarding any problem in Accessing Data Base.

Information Handling Services, 2000

1.1.1 DATA SOURCES AND TEST NUMBER PREFIXES

The data listed herein and in the Materials and Processes Technical Information System (MAPTIS) is a variety of organization. Prefix or Test numbers Inentifies these organizations as follows:

W - White Sands Test Facility (JSC)
M - Marshall Space Flight Center
FA, WDC, Philco - Ford Aerospace
G - Goddard Space Center
JPL - Jet Propulsion Laboratory
ESA,I,FC,B,ES,E - European Space Organization
SRI - Stanford Research Institution
HAC - Hughes Aircraft
R - Rockedyne

1.1.2 MATERIAL RATINGS

The material ratings listed herein are the product of an evaluation of all available test data. The rating definitions have been assigned to accurately describe all the test data. Modifications or rating changes should not change the status of materials approved by MUA or Material Lists. The new ratings should be used for all submittals after September 1988.

1.2 METALLIC MATERIALS GENERAL

Metallic materials used in the design and fabrication of space systems hardware shall be selected by considering the operational requirements for the particular application and the design engineering properties of the candidate materials. Materials are rated based on the specific criteria defined herein. Ratings are listed in Table 1 of this document. Generally, in the area of compatibility with liquid and gaseous oxygen, liquid and gaseous hydrogen, hydrazine and nitrogen, tetroxide, temper or condition is not a factor. Also, in the area of compatiblity with liquid and gaseous oxygen, if pressure is not noted, ambient pressure must be assumed.

The minimum information contained in Table 1 is as follows:

1. Material Code Index (Index Number)
2. Alloy
3. Heat Treatment
4. Generic Identification and Form
5. Material Specifications

Information Handling Services, 2000

6. Material Ratings for:

- o Corrosion (CORR)
- o Stress Corrosion Cracking (SCC)
- o Fluid Systems Compatibility
  - Gaseous Oxygen (GOX)
  - Liquid Oxygen (LOX)
  - Nitrogen Tetroxide (N_2O_4)
  - Hydrazine (HDZE)
  - LO PRESS, Hydrogen (< 450 psi)
  - HI PRESS, Hydrogen (> 450 psi)

1.2.1 NICKEL PLATING

Nickel plating shall conform to Specification QQ-N-290 (electrodeposited) or Specification MIL-C-26074 (electroless). Nickel plating should be used when the plated surfaces may be subjected to temperatures up to 1,000 'F, or when a highly corrosion resistance-surface is required. Electroless nickel is particularly adaptable on irregularly shaped parts when a uniform thickness plate is required. When a very hard nickel plating (up to Rockwell C-38) is required, Type II, Specification MIL-C-26074 (heat treated) electroless nickel should be specified. Except as otherwise approved by the procuring activity, the following minimum thickness of nickel plating shall be applied when the plating is to provide protection from corrosion.

a. Surfaces with roughness-height-rating (rhr) not greater than 32 rhr -- 0.001 inch thick (minimum).

b. Surfaces rougher than 32 rhr but not rougher than 125 rhr -- 0.0015 inch (minimum).

c. If it is considered necessary to plate surfaces exceeding 125 rhr, special precautions shall be taken to insure that the plating is free of voids or porosity that will reduce the protective effectiveness of the plating. When nickel is plated on steel heat treated from 160,000 to 180,000 psi (Rockwell C-35 to C-40), the plated part shall be baked at 400 °F + _ 25 for a minimum of 23 hours. Nickel plating on steel heat treated to 180,000 psi or above shall conform to the requirements of MIL-STD-868.

Information Handling Services, 2000

1.2.2 RATING CRITERIA

The criteria for rating metallic materials are as follows:

1.2.2.1 CORROSION RESISTANCE

Materials are rated "A" if they meet the requirements of MSFC-SPEC-250, Class II, and do not require a coating for their intended service. A "B" rating is given to those which meet this requirement, if coated. Materials rated "U" have not been tested and require verification testing prior to use and material rated "X" fails the requirements and should not be used without an approved MUA.

Materials rated other than "A" require specific corrosion protection for each application. The required protection shall be specified by the design organization and approved by the cognizant M&P organization. However, there are certain restrictions on the use of cadmium and similar coatings. The ratings given in the document for cadmium plated fasteners/steel alloys are for general corrosion only. The use of cadmium plated steels for use in sea coast/seawater environments must be avoided and is not allowed until an MUA is submitted and approved. When faying surfaces, fasteners, metals and alloys of aluminum, steel and other metals subject to sea water exposure, MSFC Drawings 10A00526, 10A00527 and 10A00528 should be consulted.

The following general information applies to cadmium plating:

a. Cadmium plating shall conform to Specification QQ-P-416. Type II, Class 2 shall be the preferred protective plating method for general applications. Type II, Class 3 should be used on close tolerance threaded parts when a minimum torquing resistance is required. The usage of cadmium plating shall be subject to the restrictions:

b. Cadmium plating shall not be used for application where the plated surfaces will be exposed to temperatures greater than 100 C. or greater.

c. Cadmium plating shall not be used where a hard or highly abrasion resistance surface is required.

d. Cadmium plating shall not be used for parts of hydraulic equipment which may be in contact with hydraulic fluids and fuels.

Information Handling Services, 2000

e. Cadmium is corroded by vapors of some organic materials and should not be used in confined areas where prolonged exposure to organic materials is possible.

f. Cadmium plating shall not be used in titanium or parts that will be in direct contact with titanium.

g. When cadmium is plated on steel heat treated 160,000 to 180,000 pounds per square inch (psi) (Rockwell C-35 to C-40) the plated part shall be baked at 375 + 25 °F for a minimum of 3 hours. Cadmium plating on steel heat treated from 180,000 to 220 psi (Rockwell C-40 to C-48) shall be baked at 375 + 25 °F for a minimum of 23 hours.

h. For cadmium plating of steel exceeding 220,000 PSI (Rockwell C-40) use vapor plating process conforming to Specification MIL-C-8837 or electroplating in accordance with Standard MIL-STD-870 when approved by procuring activity.

1.2.2.2 STRESS CORROSION CRACKING SUSCEPTIBILITY

Materials are rated "A" if they are listed in Table 1 of MSFC-SPEC-522 as having high resistance to stress corrosion. Some materials not listed in Table 1 of MSFC-SPEC-522 have been rated as "A" if evaluation of test data and/or similarity information have shown that the materials have high resistance to stress corrosion cracking. MSFC-SPEC-522 should be reviewed for more detailed instructions on stress corrosion cracking.

Materials on Table 2 of MSFC-SPEC-522 are rated "B", while materials on Table 3 are rated "C".

Materials rated "U" have not been tested and require testing to determine stress corrosion cracking susceptibility.

Materials rated "N" are not applicable to stress corrosion cracking susceptibility are not normally used in design.

Materials rated other than "A" shall be analyzed and verified in accordance with the requirements of MSFC-SPEC-522 (MUA required for "B", "C" and "U" ratings).

Information Handling Services, 2000

1.2.2.3 FLUID SYSTEM COMPATIBILITY NITROGEN TETROXIDE (N_2O_4)

Metallic materials that contact nitrogen tetroxide (N_2O_4) are rated "A", if they meet the following criteria at 360 psi:

a. Stress corrosion cracking does not occur in a time representative of the system operating life at a stress level of 75 percent of tensile yield for aluminum alloys and 95 percent of tensile yield for all other alloys and corrosion rate does not exceed one mil per year per surface.

b. Fluid decomposition is neither catalyzed nor accelerated by the metal.

c. The metal passed the fluid compatibility test of NHB 8060.1 (Test 15).

d. Metallic materials that fail the above are rated "X".

e. Untested materials are rated "U". Insufficient data is rated "I".

1.2.2.4 FLUID SYSTEM COMPATIBILITY - HYDRAZINE

Metallic materials that contact hydrazine are rated "A" if they meet the following criteria:

a. Stress corrosion cracking does not occur in a time representative of the system service life at a stress level of 75 percent of tensile yield for aluminum alloys and 95 percent of tensile yield for all other alloys.

b. Fluid decomposition is neither catalyzed nor accelerated by the metal at specified temperature of 160 F if none specified.

c. Materials that fail the above are rated "X". Untested materials are rated "U". Incomplete data is rated "I".

d. Meets requirements of Test 15 of NHB 8060.1.

NOTE: See NHB 8060.1 for "Single Barrier Failure Analysis".

Information Handling Services, 2000

1.2.2.5 COMPATIBILITY WITH LIQUID AND GASEOUS OXYGEN

Materials are rated based on results of test evaluations specified in NHB 8060.1. See 1.2.2.6 and 1.2.2.7.

1.2.2.6 TEST NO. 13 LIQUID AND GASEOUS OXYGEN MECHANICAL IMPACT

a. A -- Materials rated "A" meet the mechanical impact requirement at the indicated thickness, pressure and temperature with no reaction in 20 impacts, or one reaction out of 60 impacts, at 368 ft-lbs/in ^{2}, 72 ft-lbs or 10 Kgm, and does not require batch testing.

b. B -- Material meets the same requirements as "A" except must be batch tested (i.e., samples must be tested from each batch to insure product quality).

c. C -- Material fails at 72 ft-lbs/in ^{2} but passes at some energy level above 20 ft-lbs/in ^{2} at the test pressure, thickness and temperatures. A "C" rated material must be batch tested at threshold energy level.

d. U -- Untested

e. Z -- One or more reactions was noted at level tested. Materials rated "Z" must be further tested to determine threshold and must be batch tested.

f. X -- Material fails at 102 ft-lbs/in ^{2} (20 ft-lbs).

g. S -- Special test, see test report.

h. I -- Insufficient data

NOTE: Material Usage Agreements are required for all materials NOT rated "A". However a "B" rated material that has been batch tested and passes does not need an MUA. See NHB 8060.1 for "Single Barrier Failure Analysis".

1.2.2.7 TEST NO. 14 GASEOUS OXYGEN PNEUMATIC IMPACT

a. B -- No reactions in 20 rapid pressurization at test pressure and thickness indicated.

b. X -- Material fails the pneumatic surge test at pressure indicated.

Information Handling Services, 2000

c. U -- Untested

d. S -- Special test, see test report.

e. I -- Insufficient data

1.2.2.8 FLUID SYSTEM COMPATIBILITY - LOW PRESSURE GH_2

Metallic materials are rated "A" if there is no more than 20 percent reduction in ductility or strength in 450 psi when compared to the same test while exposed to helium.

1.2.2.9 FLUID SYSTEM COMPATIBILITY - HIGH PRESSURE GH_2

Metallic materials are rated "A" if there is no more than 20 percent reduction in ductility or strength in 5000 psi GH_2 when compared to the same test while exposed to helium.

1.3 NONMETALLIC MATERIALS GENERAL

Nonmetallic materials used in the design and fabrication of space hardware systems shall be selected by considering the operational properties for the candidate materials. Materials are rated based on the specific criteria defined herein. This list serves as a guide for material selections in both the as-designed and as-built configurations.

Minimum information contained in this list consists of:

a. Material Code
b. Material Designation
c. Material Specification and/or Manufacturer
d. Material Thickness
e. Materials are rated for:
   (1) Flammability (FLAM)
   (2) Toxicity/Offgassing (TOX)
   (3) Thermal Vacuum Stability (TVS)
   (4) Age Life (AGE)
   (5) Fluid Systems Compatibility
      (a) Nitrogen Tetroxide (N_2O_4)
      (b) Hydrazine (HDZE)
      (c) Hydraulic Fluid (HYD)
      (d) Liquid Oxygen (LOX)
      (e) High Pressure Gaseous Oxygen (HGOX) >25 psia
      (f) Liquid/Gaseous Hydrogen LH_2,GH_2

1.3.1 RATING CRITERIA AND SYMBOLS

Alpha codes are used to rate the various materials.

1.3.2 FLAMMABILITY (FLAM)

1.3.2.1 GENERAL

Materials tested per NHB 8060.1 Test 1 and 2 are rated for each test environment as follows:

a. A -- Meets Test 1, NHB 8060.1 requirement in the thickness and test condition specified.

b. B -- Material, in thickness specified, failed Test 1, NHB 8060.1 in the specific test atmosphere with a burn length of more than 6 inches but less than 12 inches.

c. C -- Material, in thickness specified, burned totally in Test 1 with flame propagation rate of less than 0.1 in Test 2.

d. U -- Untested

e. X -- Fails criteria of Test 1. Fails to meet criteria for above ratings or has moderate to heavy burn dripping.

f. S -- Special test, see test report.

g. I -- Insufficient data

NOTE: a) Solvents and liquids must pass the Flash and Fire test point above 450 °F (Test 3) to be rated acceptable.

b) The ratings for "A" rated materials in a specific oxygen concentration, thickness and pressure are applicable to the same material in the same thickness or greater at a lower oxygen concentration and/or pressure.

Information Handling Services, 2000

1.3.2.1.1 WIRE AND CABLE

Electrical wire and accessories shall be rated as follows, depending on test results in the test atmosphere during application of current overloads up to or exceeding fusion current of the electrical conductor (Test 4). Electrical wire accessories must also meet the upward flammability criteria of Test 1. Overall ratings are as follows:

a. A -- No ignition (no visible flame) with current overloads up to or exceeding fusion current of conductor and self-extinguishes in less than 3 inches when tested per Test 1.

b. B -- Ignition (visible flame) burns less than 10 seconds, damage to all other wire (excluding current carrying wire) is less than 3 inches total per Test 4 and self-extinguishes in 6 inches or less when tested per Test 1. Class B wire requires an MUA with a configuration analysis/test which will be required before final use in design.

c. C -- Fails Criteria A and B or criteria of Test 1. Fault current analysis, configuration test and MUA required before final use in design is approved. Requires cover/wrapping, etc., to isolate material.

d. U -- Untested

e. I -- Insufficient data

f. X -- Burns completely Test 1 and/or Test 4 and/or burn dripping.

1.3.2.2 TOXICITY/OFFGASSING

Unless otherwise noted, all data was normalized to a 168-hour duration and a volume of 65 cubic meters and compared with MAC Values listed in NHB 8060.1. Materials/assemblies are valid, based on an analysis of specific test results. The acceptability of all hardware in a pressurized module must be analyzed , as specified in NHB 8060.1 to determine acceptability.

Ratings are assigned as follows:

a. K -- Meets MAC (100-lbs) Values without special cure.

b. A -- Meets MAC (10-lb max) Values without special cure.

c. B -- Meets MAC (100-lbs or 10-lbs max listed in NHB 8060.1 with special cure.

d. U -- Untested

e. V -- Meets MAC (5-lbs max) Values (MUA required).

f. X -- MAC Values greater than that specified in NHB 8060.1 for the above quantities (MUA required).

Information Handling Services, 2000

g. S -- Special test, see test report.

h. I --Insufficient data

Material with unidentified trace gases will have all constituents identified treated as one gas (i.e., add up all unidentified trace gas weight). MAC for unidentified trace gases, totaled, must not exceed .1 milligrams/M^3. Cure must be specified in Materials List for "B" rated materials. Evaluation of data has indicated a wide variation in some materials rated "V" or "X". These materials may have individual test data points under same conditions that vary from "K" to "X".

NOTE: A sealed container that meets the following requirement does not require a Toxicity test for internal materials. A unit which has a leak rate of 10^{-4} standard CC/SEC or less of He, with a "partial pressure" differential of 14.7 psia.

1.3.2.3 ODOR

a. A -- Meets ODOR requirements of NHB 8060.1 without special cure.

b. B -- Meets ODOR requirements of NHB 8060.1 with special cure.

c. X -- Fails ODOR requirements.

d. U -- Untested

e. I -- Insufficient data

1.3.2.4 THERMAL VACUUM STABILITY (TVS)

Materials tested per JSC SP-R-0022A are rated as follows:

a. A -- Meets requirements of JSC SP-R-0022A without special cure/bakeout.

b. B -- Meets requirements of JSC SP-R-0022A with additional cure/bakeout.

c. C -- TML (Total Mass Loss) less than 3% (percent) and VCM (Volatile Condensable Mass) less than 1% (percent).

Information Handling Services, 2000

d. U -- Untested

e. X -- TML more than 3 and VCM more than 1.

f. S -- Special test , see test report.

g. I -- Insufficient data

MUA's must be submitted for all materials that are not "A" rated. Materials rated "B" that have been cured to meet the "A" requirements do not require an MUA if the cure data is specified on the materials list. in materials list. Data presented in the average value for the specific tests while Batch to Batch material variation has not been proven. Evaluation of data in MAPTIS from all organizations indicate a variation in TVS results a number of Materials rated "C" or "X" have individuals test under same condition that vary from "A" to "X".

1.3.2.5 STATIC AGE LIFE (AGE)

Materials are rated "A" when their properties do not deteriorate during 10 years of static life at ambient temperatures and humidity. Static life is defined as "shelf life" plus "installed life" and does not include "operational life" or "operation environment". Materials rated "B" shall meet all "A" rating requirements when specific controls are imposed (e.g., stored in a controlled environment, etc.).

1.3.2.6 FLUID SYSTEM COMPATIBILITY - NITROGEN TETROXIDE

a. Materials that contact nitrogen tetroxide (N_2O_4) are rated, "A" if they pass the fluid compatibility test of NHB 8060.1, Test 15. Materials are considered compatible if exposure to fluid for 48 hours at 160 °F does not result in chemical changes such as thickness, flaking, dissolution, etc.

b. X -- Material fails above.

c. U -- Untested

d. I -- Insufficient data

1.3.2.7 FLUID SYSTEM COMPATIBILITY - HYDRAULIC COMPATIBILITY

a. A -- Materials are rated "A" if the fluid and the material do not deteriorate appreciably on long term contact over the temperature range of -65 F to +275 °F, when tested per MIL-P-25732, and Test 15 of NHB 8060.1 and does not cause corrosion of metallic material.

Information Handling Services, 2000

b. X -- Material fails.

c. U -- Untested

d. I -- Insufficient data

1.3.2.8 FLUID SYSTEM COMPATIBILITY - HYDRAZINE

a. A -- Materials are rated "A" if they pass the fluid compatibility test of NHB 8060.1, Test

b. X -- Material Fails

c. U -- Untested

d. I -- Insufficient data

1.3.2.9 COMPATIBILITY WITH LOX/GOX

Materials are rated based on results of test evaluations specified in NHB 8060.1. See 1.3.2.10 and 1.3.2.11.

1.3.2.10 TEST NO. 13 - LIQUID AND GASEOUS OXYGEN (MECHANICAL IMPACT)

All tests for LOX/GOX compatibility shall be done at the maximum use temperature and pressure and minimum use thickness per NHB 8060.1, Test 13.

a. A -- Material meets the mechanical impact requirement at the indicated thickness, pressure and temperature with no reaction in 20 impacts, or one reaction out of 60 impacts, at 368 ft-lbs/in 2, 72 ft-lbs or 10 Kgm, and does not require batch testing.

b. B -- Same as "A" above except material must be batch tested (i.e., each batch must be tested to insure product quality).

c. C -- Material fails at 368 ft-lbs/in ^{2} but passes at some energy level above 102 ft-lbs/in ^{2} at the test pressure and temperature and must be evaluated in its use condition and must be batch tested.

d. X -- Material fails at 102 ft-lbs/in ^{2}.

e. U -- Untested

f. Z -- More than one reaction noted at test level. However, threshold energy must be determined on the actual batch used.

Information Handling Services, 2000

g. S -- Special test, see test report

h. I -- Insufficient data

NOTE: Material Usage Agreements are required for all materials not rated "A". See NHB 8060.1 for "Single Barrier Failure Analysis".

1.3.2.11 TEST 14 - GASEOUS OXYGEN PNEUMATIC IMPACT TEST

All tests for pneumatic sensitivity shall be done per NHB 8060.1 TEST 14 and rated as follows:

a. B -- No reaction in 20 surges at test pressure and thickness indicated.

b. U -- Untested

c. X -- Material fails the pneumatic surge test at pressure indicated.

d. S -- Special test, see test report.

e. I -- Insufficient data

NOTE: Material Usage Agreements are required for ALL materials NOT rated "A" . See NHB 8060.1 for "Single Barrier Failure Analysis".

1.4 STANDARD/COMMERCIAL PARTS

1.4.1 GENERAL

Standard/Commercial Parts are listed in Table 3. Their ratings are based on the criteria defined in this document and on the ratings given in Tables 1 and 2. The list serves as a guide for Standard/Commercial Parts in both the as-designed and as-built configurations. For Standard/Commercial Parts not listed in Table 3, the material ratings from Tables 1 and 2 should be used for the materials specified.

1.4.2 TABLE 3 CONTENT

Table 3 contains the listing of Standard/Commercial Parts by document number (basic part number - dash number to be added for the different sizes, lengths, etc.) and includes for each material used in the part; the assigned material code number (from Table 1 or Table 2), material designation, reference data and general ratings for each of the following:

a. F -- Flammability

Information Handling Services, 2000

b. T -- Toxicity

c. V -- Thermal/Vacuum Stability

d. A -- Static Age Life (for nonmetallics)

e. F -- Fluid Systems Compatibility (See Table 1 and/or Table 2)

f. S -- Stress Corrosion Cracking (for metallics)

g. C -- Corrosion (for metallics)

1.4.3 RATING CODES FOR STANDARD/COMMERCIAL PARTS

The following alpha characters are used in Table 3 for overall evaluation rating of the various materials used for the Standard/Commercial Parts:

a. "A" -- Materials with this rating are acceptable for use in the indicated category and include materials which have been rated "A". Also, this rating may be used for "B" rated materials which have had the necessary controls imposed to meet the "A" rating requirements, (e.g., Aluminum Alloy which has been coated with an approved corrosion protection coating).

b. "X" -- Ratings for the Standard/Commercial Parts (S/C Parts) are dependent upon the rating for each material of the part. If the rating for a material is other than the above "A" rating, the overall rating of the S/C Part is listed as "X". Use of a part with this rating should be discouraged and is not allowed until a justification is submitted and approved. The justification must contain sufficient data to justify this S/C Part selection and to support the specific design application. A Material Usage Agreement (MUA) must be submitted and approved for all S/C Parts which do not have the above "A" rating in the applicable categories.

c. "O" -- This rating is used to indicate that there is no requirement for that particular category.

d. "T" -- This rating is used to indicate that the material rating in Table 1 or Table 2 must be consulted.

1.5 FOREIGN ALLOY/CROSS REFERENCE

Listed in Tables 4 and 5 are Foreign Alloy to U.S. Alloy Cross References for selected aluminum and steel alloys.

Information Handling Services, 2000

1.6 ATOMIC OXYGEN EFFECTS

It has been observed since the early Shuttle flights that a degradation of many materials occur due to atomic oxygen interactions. Generally the effects are as follows:

a. Organic complexes containing carbon, hydrogen, oxygen and nitrogen such as polymeric films show high reactivity and have reaction efficiencies ranging from about 1 to 3 x 10- 24 cm 3 of material per incident atomic oxygen atom. Thus, these material losses are proportional to th atomic oxygen incident on the surface.

b. Fluorinated organics and silicone have relatively good stability.

c. Addition of antioxidants does not seem to significantly affect reaction rates for organics.

d. Paints which usually contain inert fillers have shown evidence of binder erosion with unaffected fillers. Binder erosion is about 10^{-21} milligrams per incident atomic oxygen atom. Optically, paints become diffuse and/or show increases in absorptivity. Some bleaching is evident in yellow urethane paint.

e. Metals such as osmium and silver show severe effects by volatilization and scaling, respectively. Degradation dependency on temperature occurs in silver. Other metals such as copper, nickel, etc., show some effects on a microscopic level. The long term effects on metals are unknown. Diffusion of oxygen into the metals may be a concern.

f. Some protective techniques which show promise include silicone based coatings, fluorinated overcoats, thin metal overcoats and metal oxide overcoats.

g. Spacecraft glow phenomena is suspected to result from the interaction of materials with atomic oxygen. Specific materials questions may be addressed to the cognizant NASA Materials and Processes organization.

1.7 TESTING

Ratings in Table 2 are based on data from the standard testing procedures of NHB 8060.1 and SP-R-0022A. Samples of materials requiring test shall be submitted in amounts specified in Table 6.

1.8 SAFETY

Safe practices shall be assured in accordance with all applicable documents.

Information Handling Services, 2000

1.9 PAYLOAD BAY HARDWARE IN VENTED CONTAINERS

Pallet hardware may be categorized as vented or sealed containers. This hardware may include high voltage or small gas filled cells, special electronics, lamps, etc. The hardware must be evaluated per NHB 8060.1 to assure safety while exposed to the ambient environment before launch and after landing. Evaluation will be at the black-box level. Also, the pallet experiments shall be judged for vacuum compatibility per JSC SP-R-0022A, "Vacuum Stability Requirements of Polymeric Materials for Spacecraft Applications".

NOTE: A sealed unit is defined as a unit which has a leak rate of 1×10^{-4} standard CC/SEC or less of He with a pressure difference of 14.7 psi.

2.0 GROUND SUPPORT EQUIPMENT (GSE)

GSE shall, in no way, adversely effect the flight hardware. That which interfaces with flight hardware, shall be treated as flight hardware. This document also is applicable to GSE used for/in major test and manned test chambers.

3.0 CONTROL OF MATERIALS OTHER THAN "A" RATED

Acceptable materials are those which are rated "A" per paragraph 1.3.2 herein. "B" rated materials as well as all other materials which failed NHB 8060.1, require an MUA or other documentation as specified by the cognizant NASA Center for approval of usage.

4.0 IDENTIFICATION OF MATERIALS

All materials and parts must be identified by specification, material, manufacturer's trade name and manufacturer.

5.0 EXPLANATION OF TERMS

Material Code is used herein for reference as Material Code Directory number, also called Index Number. See paragraph 10.0 for acronyms.

6.0 ADDITIONAL INFORMATION

The information in Tables 1 and 2 is sorted as follows:

a. METALS

(1) Material Code
(2) Designation
(3) Specification

Information Handling Services, 2000

b. NONMETALS

(1) Material Code
(2) Designation
(3) Specification
(4) Manufacturer

c. A listing of constituent gases is contained in the MAPTIS system.

d. Contact C. F. Key, Marshall Space Flight Center, Code EH02, telephone (205) 544-2487 or DR. L. J. LEGER, Johnson Space Center, Code ES5, telephone (713) 483-8913 for additional information or comments.

7.0 HANDBOOK SEARCH HINTS

NOTE: MATERIAL RATINGS ARE LISTED ONLY IN DESIGNATION TABLES.

INFORMATION YOU WILL SUPPLY :
(1) 'MATERIAL CODE' EXAMPLE '06173'
(2) 'MATERIAL MANUFACTURER' EXAMPLE 'LORD CORPORATION'
(3) 'MATERIAL SPECIFICATION' EXAMPLE 'MIL-P-23377'
(4) 'MATERIAL DESIGNATION/USE' EXAMPLE 'COATING CHEMGLAZE Z306'
EXAMPLE 'AL 2024'

USE APPLICABLE TABLE TO LOCATE CORRECT DESIGNATION FROM INFORMATION SUPPLIED.

SEARCH HINTS ARE AS FOLLOW:
(1) HEAT SHRINKABLE TUBING -- SEE 'TUBING'
(2) ADHESIVE -- SEE 'ADHESIVE'
(3) COATING -- SEE 'COATING'
(4) TAPE -- SEE 'TAPE'
(5) RUBBER -- SEE 'RUBBER'
(6) LUBRICANT -- SEE 'LUBE GREASE', 'LUBE OIL', ETC.
(7) PRINTED WIRING BOARD -- SEE 'LAMIN' OR 'LAMINATE'
(8) INSULATION -- SEE 'INSULATION'
(9) MULTI-LAYER INSULATION -- SEE 'MLI'
(10) FABRIC -- SEE 'FABRIC'
(11) THREAD -- SEE 'THREAD' OR 'YARN'
(12) 2024T6 -- SEE 'AL 2024T6'
(13) 304 -- SEE 'CRES 304'

SOME MATERIAL MAY HAVE MORE THAN ONE USAGE CATEGORY SUCH AS: 'SEALANTS', 'ADHESIVE', 'RUBBER'. ALL OF THESE CATEGORIES SHOULD BE SEARCHED BEFORE DETERMINING THE MATERIAL IS NOT IN HANDBOOK.

SEE TABLES 1C AND 2C FOR 'DELETED' MATERIAL CODES AND REPLACEMENTS.

SPECIFICATIONS AND MANUFACTURERS ARE NOT DUPLICATED FOR MULTIPLE USES. THEY ARE ONLY PRINTED FOR FIRST (1st) DESIGNATION.

Information Handling Services, 2000

8.0 ADDITION OF MATERIALS/STANDARD COMMERCIAL PARTS TO SELECTION LIST

When materials and/or standard commercial parts are used that are not listed herein, the cognizant person, listed in 7.0C must be contacted to determine what information and/or test data is required prior to assigning a material code. In addition, the following data input sheets must be submitted:

a. Selection List Data Sheets (Figures 1 or 2) shall be used to request that new materials be palced into the Materials Selection List.

b. The Standard/Commercial Parts Data Input Sheet (Figure 3) shall be used to request that a standard commercial part be added to the Standard/Commercial Parts Report.

9.0 ADDENDA/UPDATES

The tables attached herein will be updated quarterly. Please submit written requests for updates/addendums to C. F. Key at the address specified in paragraph 7.0.

10.0 ACRONYMS

FLAMMABILITY								
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
a	b	c	d	e	f	g	h	i

FLAMMABILITY
a Rating
b NHB 8060 test number
c Test fluid oxygen, percent
d Test pressure, psia
e Sample thickness, inches
f Substrate thickness, inches
g Combustion rate, inches/sec; 'T' in last character indicates total burn
h Burn length, inches
i Dirp burn, mass transfer

OXYGEN COMP							
RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
a	b	c	d	e	f	g	h

OXYGEN COMPATIBILITY
a Rating
b Mechanical or pneumatic
c Test pressure, psia
d Impact energy, ft-lbs
e Test temperature, Fahrenheit
f Thickness, inches
g Number of reactions
h Number of tests

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
a	b	c	d	e	f

THERMAL VACUUM STABILITY
a Rating
b Pressure, 10^{-X} TORR
c Total mass loss, percent
d Volatile condensible, percent
e Recovered mass loss, percent
f Cure/bake out conditions, hour and Fahrenheit

FSC	
RT	FLUID NAME
a	b

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
a	a	b	c

FLUID SYSTEMS COMPATIBILITY
a Rating
b Test fluid
ODOR
a Rating
TOXICITY
a Rating
b Sample weight, grams
c Cure/bake out conditions, hour and Fahrenheit

Information Handling Services, 2000

10.1 CURE INFORMATION

Cures are presented as follows:

a. 24Hrs RT/24Hrs 150 °F

b. 2 days RT/5 days RT/4Hrs 150 °F

These should be encoded as follows:

a. 24hrs at room temperature followed by 24hrs at 150 °F

b. 2 days at room temperature followed by 5 days at room temperature followed by 4hrs at 150 °F

Cure order must not be modified.

Information Handling Services, 2000

TABLES

(1 - 5)

Information Handling Services, 2000

TABLE 1

METALS

Information Handling Services, 2000

TABLE 1A

METALS BY DESIGNATION

Information Handling Services, 2000

DATE: 12/23/88
METALS BY DESIGNATION

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10612	65CU-18NI-17ZNALLOY NO 752 SPEC: ASTM-B-122 #2		B	C	U		U	U		U		U	U		
50235	AISI 7MG TUNGSTEN OXIDE MANF: FAIR-RITE		U	U	U		U	U		U		U	U		
50202	AL 1050 NOC		U	A	A		A	U		U		U	U		
52698	AL 1050-H112 TUBE EXTRUDED COILED		B	A	A		A	U		U		U	U		
52081	AL 1060-H112 BAR EXTRUDED SPEC: ASTM B221		B	A	A		A	U		U		U	U		
52570	AL 1060-H112 PIPE SPEC: ASTM B345		B	A											
52065	AL 1060-H112 PLATE SPEC: ASTM B209		B	A											
52083	AL 1060-H112 ROD EXTRUDED SPEC: ASTM B221		B	A											
52079	AL 1060-H112 SHAPES EXTRUDED SPEC: ASTM B221		B	A											
52061	AL 1060-H112 SHEET SPEC: ASTM B209		B	A											
52077	AL 1060-H112 TUBE EXTRUDED SPEC: ASTM B221	ASTM B241	B	A											
52085	AL 1060-H112 WIRE EXTRUDED SPEC: ASTM B221		B	A											
52090	AL 1060-H113 TUBE DRAWN SPEC: ASTM B210	ASTM B483	B	A											
52063	AL 1060-H12 PLATE SPEC: ASTM B209		B	A											
52057	AL 1060-H12 SHEET SPEC: ASTM B209		B	A											
52087	AL 1060-H12 TUBE DRAWN SPEC: ASTM B210	ASTM B483	B	A											
52074	AL 1060-H14 BAR ROLLED SPEC: ASTM B211		B	A											
52064	AL 1060-H14 PLATE SPEC: ASTM B209		B	A											

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52071	AL 1060-H14 ROD ROLLED SPEC: ASTM B211		B	A											
52058	AL 1060-H14 SHEET SPEC: ASTM B209		B	A											
52091	AL 1060-H14 TUBE CONDENSER SPEC: ASTM B221		B	A											
52088	AL 1060-H14 TUBE DRAWN SPEC: ASTM B210	ASTM B483	B	A											
52566	AL 1060-H14 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
52555	AL 1060-H14 WIRE COLD FINISHED SPEC: ASTM B211		B	A											
52068	AL 1060-H14 WIRE ROLLED SPEC: ASTM B211		B	A											
52059	AL 1060-H16 SHEET SPEC: ASTM B209		B	A											
52562	AL 1060-H18 BAR COLD FINISHED SPEC: ASTM B211		B	A											
52075	AL 1060-H18 BAR ROLLED SPEC: ASTM B211		B	A											
52559	AL 1060-H18 ROD COLD FINISHED SPEC: ASTM B211		B	A											
52072	AL 1060-H18 ROD ROLLED SPEC: ASTM B211		B	A											
52060	AL 1060-H18 SHEET SPEC: ASTM B209		B	A											
52089	AL 1060-H18 TUBE DRAWN SPEC: ASTM B210	ASTM B483	B	A											
52567	AL 1060-H18 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
52556	AL 1060-H18 WIRE COLD FINISHED SPEC: ASTM B211		B	A											
52069	AL 1060-H18 WIRE ROLLED SPEC: ASTM B211		B	A											

MSFC-HDBK-527 REV F 9999942 0004822 5

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52560	AL 1060-O BAR COLD FINISHED SPEC: ASTM B211		B	A											
52080	AL 1060-O BAR EXTRUDED SPEC: ASTM B221		B	A											
52073	AL 1060-O BAR ROLLED SPEC: ASTM B211		B	A											
52569	AL 1060-O PIPE SPEC: ASTM B345		B	A											
52062	AL 1060-O PLATE SPEC: ASTM B209		B	A											
52557	AL 1060-O ROD COLD FINISHED SPEC: ASTM B211		B	A											
52082	AL 1060-O ROD EXTRUDED SPEC: ASTM B221		B	A											
52070	AL 1060-O ROD ROLLED SPEC: ASTM B211		B	A											
52078	AL 1060-O SHAPES EXTRUDED SPEC: ASTM B221		B	A											
52056	AL 1060-O SHEET SPEC: ASTM B209		B	A											
52092	AL 1060-O TUBE CONDENSER SPEC: ASTM B404		B	A											
52086	AL 1060-O TUBE DRAWN SPEC: ASTM B210	ASTM B483	B	A											
52564	AL 1060-O TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
52076	AL 1060-O TUBE EXTRUDED SPEC: ASTM B221	ASTM B241	B	A											
52563	AL 1060-O TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
52554	AL 1060-O WIRE COLD FINISHED SPEC: ASTM B211		B	A											
52084	AL 1060-O WIRE EXTRUDED SPEC: ASTM B221		B	A											

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52067	AL 1060-O WIRE ROLLED SPEC: ASTM B211		B	A											
10217	AL 1100 BAR SPEC: QQ-A-225/1	QQ-A-430	B	A	A	1000	A	A		A		A	A		
50532	AL 1100 ROD SPEC: QQ-A-225/1	QQ-A-430	B	A	A		A	A		A		A	A		
10366	AL 1100 SHEET ANNEALED SPEC: QQ-A-250/1		B	A	A		A	A		A		A	A		
50298	AL 1100 SHEET CLAD SPEC: QQ-A-250/1		B	A	A		A	A		A		A	A		
50533	AL 1100 WIRE SPEC: QQ-A-225/1	QQ-A-430	B	A	A			A		A		A	A		
52585	AL 1100-F BAR COLD FINISHED SPEC: AMS 4102		B	A											
51974	AL 1100-F BAR ROLLED SPEC: AMS 4102		B	A											
52584	AL 1100-F ROD COLD FINISHED SPEC: AMS 4102		B	A											
51973	AL 1100-F ROD ROLLED SPEC: AMS 4102		B	A											
52583	AL 1100-F WIRE COLD FINISHED SPEC: AMS 4102		B	A											
51972	AL 1100-F WIRE ROLLED SPEC: AMS 4102		B	A											
52582	AL 1100-H112 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/1	B	A											
51976	AL 1100-H112 BAR EXTRUDED SPEC: ASTM B221		B	A											
51971	AL 1100-H112 BAR ROLLED SPEC: ASTM B211	QQ-A-225/1	B	A											
52003	AL 1100-H112 FORGING DIE SPEC: ASTM B247		B	A											
51961	AL 1100-H112 PLATE SPEC: ASTM B209	QQ-A-250/1	B	A											

MSFC-HDBK-527 REV F 9999942 0004824 9

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52581	AL 1100-H112 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/1	B	A											
51978	AL 1100-H112 ROD EXTRUDED SPEC: ASTM B221		B	A											
51970	AL 1100-H112 ROD ROLLED SPEC: ASTM B211	QQ-A-225/1	B	A											
51982	AL 1100-H112 SHAPES EXTRUDED SPEC: ASTM B221		B	A											
52588	AL 1100-H112 TUBE COILED EXTRUDED SPEC: ASTM B491		B	A											
51984	AL 1100-H112 TUBE EXTRUDED SPEC: ASTM B221 ASTM B491	ASTM B241	B	A											
52587	AL 1100-H112 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
52580	AL 1100-H112 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/1	B	A											
51980	AL 1100-H112 WIRE EXTRUDED SPEC: ASTM B221		B	A											
51969	AL 1100-H112 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/1	B	A											
51989	AL 1100-H113 TUBE DRAWN SPEC: ASTM B210 WW-T-700/1	ASTM B483	B	A											
52593	AL 1100-H113 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/1	B	A											
51958	AL 1100-H12 PLATE SPEC: ASTM B209	QQ-A-250/1	B	A											
51957	AL 1100-H12 SHEET SPEC: ASTM B209	QQ-A-250/1	B	A											
51985	AL 1100-H12 TUBE DRAWN SPEC: ASTM B210 WW-T-700/1	ASTM B483	B	A											
52590	AL 1100-H12 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/1	B	A											

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0004825 0

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51992	AL 1100-H12 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
52576	AL 1100-H12 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/1	B	A											
51965	AL 1100-H12 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/1	B	A											
50974	AL 1100-H14 PLATE SPEC: AMS 4003 QQ-A-250/1	ASTM B209	B	A											
52000	AL 1100-H14 ROD RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											
50975	AL 1100-H14 SHEET SPEC: AMS 4003 QQ-A-250/1	ASTM B209	B	A											
51986	AL 1100-H14 TUBE DRAWN SPEC: AMS 4062	ASTM B483	B	A											
51990	AL 1100-H14 TUBE DRAWN SEAMLESS SPEC: AMS 4062		B	A											
51993	AL 1100-H14 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
52577	AL 1100-H14 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/1	B	A											
51998	AL 1100-H14 WIRE RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											
51966	AL 1100-H14 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/1	B	A											
51959	AL 1100-H16 SHEET SPEC: ASTM B209	QQ-A-250/1	B	A											
51987	AL 1100-H16 TUBE DRAWN SPEC: ASTM B210 WW-T-700/1	ASTM B483	B	A											
52591	AL 1100-H16 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/1	B	A											
51994	AL 1100-H16 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52578	AL 1100-H16 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/1	B	A											
51967	AL 1100-H16 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/1	B	A											
51960	AL 1100-H18 SHEET SPEC: ASTM B209	QQ-A-250/1	B	A											
51988	AL 1100-H18 TUBE DRAWN SPEC: ASTM B210 WW-T-700/1	ASTM B483	B	A											
52592	AL 1100-H18 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/1	B	A											
51996	AL 1100-H18 TUBE WELDED SPEC: ASTM B313		B	A											
52579	AL 1100-H18 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/1	B	A											
51968	AL 1100-H18 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/1	B	A											
52005	AL 1100-H19 FOIL SPEC: QQ-A-1876		B	A											
52002	AL 1100-H24 ROD RIVET AND COLD HEADING SPEC: QQ-A-430C		B	A											
52001	AL 1100-H24 WIRE RIVET AND COLD HEADING SPEC: QQ-A-430C		B	A											
52575	AL 1100-O BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/1	B	A											
51975	AL 1100-O BAR EXTRUDED SPEC: ASTM B221		B	A	A		A	A		A		A	A		
51964	AL 1100-O BAR ROLLED SPEC: ASTM B211	QQ-A-225/1	B	A	A		A	A		A		A	A		
52004	AL 1100-O FOIL SPEC: QQ-A-1876		B	A	A		A	A		A		A	A		
50534	AL 1100-O PLATE SPEC: AMS 4001 QQ-A-250/1	ASTM B209	B	A	A		A	A		A		A	A		
52574	AL 1100-O ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/1	B	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004827 4

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51977	AL 1100-O ROD EXTRUDED SPEC: ASTM B221		B	A	A		A	A		A		A	A		
51999	AL 1100-O ROD RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A	A		A	A		A		A	A		
51963	AL 1100-O ROD ROLLED SPEC: ASTM B211	QQ-A-225/1	B	A	A		A	A		A		A	A		
51981	AL 1100-O SHAPES EXTRUDED SPEC: ASTM B221		B	A	A		A	A		A		A	A		
10279	AL 1100-O SHEET SPEC: AMS 4001 QQ-A-250/1	ASTM B209	B	A	A	1000	A	A		A		A	A		
10340	AL 1100-O TUBE SPEC: ASTM B210 WW-T-700/1	ASTM B483	B	A	A	1000	A	A		A		A	A		
52697	AL 1100-O TUBE DRAWN SPEC: ASTM B210 WW-T-700/1	ASTM B483	B	A	A		A	A		A		A	A		
52589	AL 1100-O TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/1	B	A	A		A	A		A		A	A		
51983	AL 1100-O TUBE EXTRUDED SPEC: ASTM B221	ASTM B241	B	A	A		A	A		A		A	A		
52586	AL 1100-O TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A	A		A	A		A		A	A		
51991	AL 1100-O TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A	A		A	A		A		A	A		
52573	AL 1100-O WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/1	B	A	A		A	A		A		A	A		
51979	AL 1100-O WIRE EXTRUDED SPEC: ASTM B221		B	A	A		A	A		A		A	A		
51997	AL 1100-O WIRE RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A	A		A	A		A		A	A		
51962	AL 1100-O WIRE ROLLED SPEC: ASTM B211	QQ-A-225/1	B	A	A		A	A		A		A	A		
51700	AL 1145-H19 FOIL SPEC: ASTM B373	QQ-A-1876	B	A											

MSFC-HDBK-527 REV F 9999942 0004828 6

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51699	AL 1145-O FOIL SPEC: ASTM B373	QQ-A-1876	B	A											
51181	AL 1175		B	A											
10684	AL 1175-O CASTING SAND,MOLD,DIE SPEC: ASTM B179		B	A	A		A	A		A		A	A		
10348	AL 11XX FOIL ANNEALED SPEC: QQ-A-1876		B	A	A		A	A		A		A	A		
51182	AL 1200-H112 TUBE EXTRUDED COILED		B	A											
51172	AL 1230		B	A											
51827	AL 1235-H111 TUBE EXTRUDED ROUND SPEC: ASTM B491		B	A											
51828	AL 1235-H112 TUBE EXTRUDED ROUND SPEC: ASTM B491		B	A											
51044	AL 1345		B	A											
51592	AL 1350 CONDUCTOR SOLID ROUND SPEC: ASTM B609		B	A											
51591	AL 1350-H14 WIRE SPEC: ASTM B314	ASTM B323	B	A											
51590	AL 1350-H19 WIRE SPEC: ASTM B230		B	A											
50248	AL 2011-T3 BAR SPEC: QQ-A-225/3	RB0170-236	B	C	A		A	A		A		A	A		
52544	AL 2011-T3 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/3	B	C	A		A	A		A		A	A		
52013	AL 2011-T3 BAR ROLLED SPEC: ASTM B211	QQ-A-225/3	B	C	A		A	A		A		A	A		
52540	AL 2011-T3 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/3	B	C	A		A	A		A		A	A		
52009	AL 2011-T3 ROD ROLLED SPEC: ASTM B211	QQ-A-225/3	B	C	A		A	A		A		A	A		
52006	AL 2011-T3 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	C	A		A	A		A		A	A		
50536	AL 2011-T3 WIRE SPEC: QQ-A-225/3		B	C	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004829 8

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52548	AL 2011-T3 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/3	B	C	A		A	A		A		A	A		
52017	AL 2011-T3 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/3	B	C	A		A	A		A		A	A		
52545	AL 2011-T4 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/3	B	C											
52014	AL 2011-T4 BAR ROLLED SPEC: ASTM B211	QQ-A-225/3	B	C											
52541	AL 2011-T4 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/3	B	C											
52010	AL 2011-T4 ROD ROLLED SPEC: ASTM B211	QQ-A-225/3	B	C											
52552	AL 2011-T4 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/3	B	C											
52550	AL 2011-T4 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/3	B	C											
52546	AL 2011-T451 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/3	B	C											
52015	AL 2011-T451 BAR ROLLED SPEC: ASTM B211	QQ-A-225/3	B	C											
52542	AL 2011-T451 ROD COLD FINISHED SPEC: ASTM-B211	QQ-A-225/3	B	C											
52011	AL 2011-T451 ROD ROLLED SPEC: ASTM B211	QQ-A-225/3	B	C											
52553	AL 2011-T451 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/3	B	C											
52551	AL 2011-T451 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/3	B	C											
52007	AL 2011-T4511 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	C											
30135	AL 2011-T6 BAR SPEC: QQ-A-225/3		B	B	U		U	U		U		U	U		
50537	AL 2011-T6 ROD SPEC: QQ-A-225/3		B	B	U		U	U		U		U	U		

MSFC-HDBK-527 REV F 9999942 0004830 4

Information Handling Services, 2000

DATE: 12/23/88
METALS BY DESIGNATION

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50538	AL 2011-T6 WIRE SPEC: QQ-A-225/3		B	A	U		U	U		U		U	U		
50249	AL 2011-T8 BAR SPEC: QQ-A-225/3	RBO170-236	B	A	A		A	A		A		A			
52547	AL 2011-T8 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/3	B	A	A		A	A		A		A			
52016	AL 2011-T8 BAR ROLLED SPEC: ASTM B211	QQ-A-225/3	B	A	A		A	A		A		A	A		
50539	AL 2011-T8 ROD SPEC: QQ-A-225/3		B	A	A		A	A		A		A			
52543	AL 2011-T8 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/3	B	A	A		A	A		A		A			
52012	AL 2011-T8 ROD ROLLED SPEC: ASTM B211	QQ-A-225/3	B	A	A		A	A		A		A			
52008	AL 2011-T8 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A	A		A	A		A		A			
50540	AL 2011-T8 WIRE SPEC: QQ-A-225/3		B	A	A		A	A		A		A			
52549	AL 2011-T8 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/3	B	A	A		A	A		A		A			
52018	AL 2011-T8 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/3	B	A	A		A	A		A		A			
52421	AL 2014 FORGING STOCK SPEC: AMS 4133		B	N											
51527	AL 2014-O BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	N											
52334	AL 2014-O BAR DRAWN SPEC: QQ-A-225/4		B	N											
52355	AL 2014-O BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	N											
51520	AL 2014-O BAR ROLLED SPEC: ASTM B211	QQ-A-225/4	B	N											
52423	AL 2014-O IMPACTS SPEC: MIL-A-12545		B	N											

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51510	AL 2014-O PLATE SPEC: AMS 4028	ASTM B209	B	N											
51550	AL 2014-O PLATE CLAD SPEC: ASTM B209		B	N											
52313	AL 2014-O ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	N											
52341	AL 2014-O ROD DRAWN SPEC: QQ-A-225/4		B	N											
52364	AL 2014-O ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	N											
52306	AL 2014-O ROD ROLLED SPEC: ASTM B211	QQ-A-225/4	B	N											
52373	AL 2014-O SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	N											
51504	AL 2014-O SHEET SPEC: AMS 4028	ASTM B209	B	N											
51549	AL 2014-O SHEET CLAD SPEC: ASTM B209		B	N											
52409	AL 2014-O TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	N											
52382	AL 2014-O TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/2	ASTM B241	B	N											
52400	AL 2014-O TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	N											
52327	AL 2014-O WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	N											
52348	AL 2014-O WIRE DRAWN SPEC: QQ-A-225/4		B	N											
52391	AL 2014-O WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	N											
52320	AL 2014-O WIRE ROLLED SPEC: ASTM B211	QQ-A-225/4	B	N											
51505	AL 2014-T3 SHEET SPEC: ASTM B209		B	B											

MSFC-HDBK-527 REV F 9999942 0004832 8

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51551	AL 2014-T3 SHEET CLAD SPEC: ASTM B209		B	B											
51528	AL 2014-T4 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	C											
52335	AL 2014-T4 BAR DRAWN SPEC: QQ-A-225/4		B	C											
52356	AL 2014-T4 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
51521	AL 2014-T4 BAR ROLLED SPEC: ASTM B211	QQ-A-225/4	B	C											
52422	AL 2014-T4 FORGING SPEC: AMS 4134		B	C											
52415	AL 2014-T4 FORGING DIE SPEC: ASTM B247	QQ-A-367	B	C											
52424	AL 2014-T4 IMPACTS SPEC: MIL-A-12545		B	C											
52314	AL 2014-T4 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	C											
52342	AL 2014-T4 ROD DRAWN SPEC: QQ-A-225/4		B	C											
52365	AL 2014-T4 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
52307	AL 2014-T4 ROD ROLLED SPEC: ASTM B211	QQ-A-225/4	B	C											
52374	AL 2014-T4 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
51506	AL 2014-T4 SHEET SPEC: ASTM B209		B	B											
51552	AL 2014-T4 SHEET CLAD SPEC: ASTM B209		B	B											
52410	AL 2014-T4 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	B											
52383	AL 2014-T4 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/2	ASTM B241	B	B											

MSFC-HDBK-527 REV F 9999942 0004833 T

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52401	AL 2014-T4 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
52328	AL 2014-T4 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	B											
53027	AL 2014-T4 WIRE DRAWN SPEC: QQ-A-225/4		B	B											
52392	AL 2014-T4 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	B											
52321	AL 2014-T4 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/4	B	B											
51529	AL 2014-T42 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	C											
52336	AL 2014-T42 BAR DRAWN SPEC: QQ-A-225/4		B	C											
52359	AL 2014-T42 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
51522	AL 2014-T42 BAR ROLLED SPEC: ASTM B211	QQ-A-225/4	B	C											
51511	AL 2014-T42 PLATE SPEC: ASTM B209		B	C											
51554	AL 2014-T42 PLATE CLAD SPEC: ASTM B209		B	C											
52315	AL 2014-T42 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	C											
52343	AL 2014-T42 ROD DRAWN SPEC: QQ-A-225/4		B	C											
52368	AL 2014-T42 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
52308	AL 2014-T42 ROD ROLLED SPEC: ASTM B211	QQ-A-225/4	B	C											
52377	AL 2014-T42 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
51507	AL 2014-T42 SHEET SPEC: ASTM B209		B	B											

MSFC-HDBK-527 REV F 9999942 0004834 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51553	AL 2014-T42 SHEET CLAD SPEC: ASTM B209		B	B											
52411	AL 2014-T42 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	B											
52386	AL 2014-T42 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/2	ASTM B241	B	B											
52404	AL 2014-T42 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
52329	AL 2014-T42 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	B											
52350	AL 2014-T42 WIRE DRAWN SPEC: QQ-A-225/4		B	B											
52395	AL 2014-T42 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	B											
52322	AL 2014-T42 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/4	B	B											
51530	AL 2014-T451 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	C											
52337	AL 2014-T451 BAR DRAWN SPEC: QQ-A-225/4		B	C											
51523	AL 2014-T451 BAR ROLLED SPEC: ASTM B211	QQ-A-225/4	B	C											
51512	AL 2014-T451 PLATE SPEC: ASTM B209		B	C											
51555	AL 2014-T451 PLATE CLAD SPEC: ASTM B209		B	C											
52316	AL 2014-T451 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	C											
52344	AL 2014-T451 ROD DRAWN SPEC: QQ-A-225/4		B	C											
52309	AL 2014-T451 ROD ROLLED SPEC: ASTM B211	QQ-A-225/4	B	C											
52330	AL 2014-T451 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	B											

MSFC-HDBK-527 REV F 9999942 0004835 3

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52351	AL 2014-T451 WIRE DRAWN SPEC: QQ-A-225/4		B	B											
52323	AL 2014-T451 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/4	B	B											
52357	AL 2014-T4510 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
52366	AL 2014-T4510 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
52375	AL 2014-T4510 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
52384	AL 2014-T4510 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/2	ASTM B241	B	B											
52402	AL 2014-T4510 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
52393	AL 2014-T4510 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	B											
52358	AL 2014-T4511 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
52367	AL 2014-T4511 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
52376	AL 2014-T4511 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
52385	AL 2014-T4511 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/2	ASTM B241	B	B											
52403	AL 2014-T4511 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
52394	AL 2014-T4511 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	B											
50220	AL 2014-T6 BAR COLD FINISHED SPEC: AMS 4121 QQ-A-225/4	ASTM B211	B	C	A		A	A		A		A	A		
52338	AL 2014-T6 BAR DRAWN SPEC: AMS 4121	QQ-A-225/4	B	C	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004836 5

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52360	AL 2014-T6 BAR EXTRUDED SPEC: AMS 4153 QQ-A-200/2	ASTM B221	B	C	A		A	A		A		A	A		
53028	AL 2014-T6 BAR ROLLED SPEC: AMS 4121 QQ-A-225/4	ASTM B211	B	C	A		A	A		A		A	A		
52420	AL 2014-T6 FORGING SPEC: AMS 4133	AMS 4135	B	C	A		A	A		A		A	A		
52414	AL 2014-T6 FORGING DIE SPEC: ASTM B247 QQ-A-367	MIL-A-22771	B	C	A		A	A		A		A	A		
52416	AL 2014-T6 FORGING HAND SPEC: ASTM B247 QQ-A-367	MIL-A-22771	B	C	A		A	A		A		A	A		
52425	AL 2014-T6 IMPACTS SPEC: MIL-A-12545		B	C	A		A	A		A		A	A		
51517	AL 2014-T6 PLATE		B	C	A		A	A		A		A	A		
50541	AL 2014-T6 PLATE CLAD SPEC: QQ-A-250/3		B	C	A		A	A		A		A	A		
52418	AL 2014-T6 RINGS ROLLED SPEC: MIL-A-22771		B	C	A		A	A		A		A	A		
52317	AL 2014-T6 ROD COLD FINISHED SPEC: AMS 4121 QQ-A-225/4	ASTM B211	B	C	A		A	A		A		A	A		
52345	AL 2014-T6 ROD DRAWN SPEC: AMS 4121	QQ-A-225/4	B	C	A		A	A		A		A	A		
52369	AL 2014-T6 ROD EXTRUDED SPEC: AMS 4153 QQ-A-200/2	ASTM B221	B	C	A		A	A		A		A	A		
52310	AL 2014-T6 ROD ROLLED SPEC: AMS 4121 QQ-A-225/4	ASTM B211	B	C	A		A	A		A		A	A		
52378	AL 2014-T6 SHAPES EXTRUDED SPEC: AMS 4153 QQ-A-200/2	ASTM B221	B	C	A		A	A		A		A	A		
51508	AL 2014-T6 SHEET SPEC: AMS 4029	ASTM B209	B	B	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004837 7

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10521	AL 2014-T6 SHEET CLAD SPEC: ASTM B209	QQ-A-250/3	B	B	A		A	A		A		A			
52412	AL 2014-T6 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	B	A		A	A		A		A	A		
52387	AL 2014-T6 TUBE EXTRUDED SPEC: AMS 4153 ASTM B241	ASTM B221 QQ-A-200/2	B	B	A		A	A		A		A	A		
52405	AL 2014-T6 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B	A		A	A		A		A	A		
52331	AL 2014-T6 WIRE COLD FINISHED SPEC: AMS 4121 QQ-A-225/4	ASTM B211	B	B	A		A	A		A		A	A		
52349	AL 2014-T6 WIRE DRAWN SPEC: AMS 4121	QQ-A-225/4	B	B	B		B	B		B		B	B		
52396	AL 2014-T6 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	B	A		A	A		A		A	A		
52324	AL 2014-T6 WIRE ROLLED SPEC: AMS 4121 QQ-A-225/4	ASTM B211	B	B	A		A	A		A		A	A		
51532	AL 2014-T62 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	C											
52339	AL 2014-T62 BAR DRAWN SPEC: QQ-A-225/4		B	C											
52363	AL 2014-T62 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
51525	AL 2014-T62 BAR ROLLED SPEC: ASTM B211	QQ-A-225/4	B	C											
51513	AL 2014-T62 PLATE SPEC: ASTM B209		B	C											
50542	AL 2014-T62 PLATE CLAD SPEC: ASTM B209	QQ-A-250/3	B	C	C		A	A		A		A	A		
52318	AL 2014-T62 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	C											
52346	AL 2014-T62 ROD DRAWN SPEC: QQ-A-225/4		B	C											

MSFC-HDBK-527 REV F 9999942 0004838 9

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52372	AL 2014-T62 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
52311	AL 2014-T62 ROD ROLLED SPEC: ASTM B211	QQ-A-225/4	B	C											
52381	AL 2014-T62 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
51509	AL 2014-T62 SHEET SPEC: ASTM B209		B	B											
50251	AL 2014-T62 SHEET CLAD SPEC: ASTM B209	QQ-A-250/3	B	B	C		A	A		A		A	A		
52413	AL 2014-T62 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	B											
52390	AL 2014-T62 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/2	ASTM B241	B	B											
52408	AL 2014-T62 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
52332	AL 2014-T62 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	B											
52353	AL 2014-T62 WIRE DRAWN SPEC: QQ-A-225/4		B	B											
52399	AL 2014-T62 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	B											
52325	AL 2014-T62 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/4	B	B											
51533	AL 2014-T651 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	C											
52340	AL 2014-T651 BAR DRAWN SPEC: QQ-A-225/4		B	C											
51526	AL 2014-T651 BAR ROLLED SPEC: ASTM B211	QQ-A-225/4	B	C											
51514	AL 2014-T651 PLATE SPEC: AMS 4014	ASTM B209	B	C											
51556	AL 2014-T651 PLATE CLAD SPEC: ASTM B209		B	C											

MSFC-HDBK-527 REV F 9999942 0004839 0

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52319	AL 2014-T651 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	C											
52347	AL 2014-T651 ROD DRAWN SPEC: QQ-A-225/4		B	C											
52312	AL 2014-T651 ROD ROLLED SPEC: ASTM B211	QQ-A-225/4	B	C											
52333	AL 2014-T651 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/4	B	B											
52354	AL 2014-T651 WIRE DRAWN SPEC: QQ-A-225/4		B	B											
52326	AL 2014-T651 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/4	B	B											
52361	AL 2014-T6510 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
52370	AL 2014-T6510 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
52379	AL 2014-T6510 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
52388	AL 2014-T6510 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/2	ASTM B241	B	B											
52406	AL 2014-T6510 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
52397	AL 2014-T6510 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	B											
52362	AL 2014-T6511 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
52371	AL 2014-T6511 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
52380	AL 2014-T6511 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	C											
52389	AL 2014-T6511 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/2	ASTM B241	B	B											
52407	AL 2014-T6511 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											

MSFC-HDBK-527 REV F 9999942 0004840 7

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52398	AL 2014-T6511 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/2	B	B											
52417	AL 2014-T652 FORGING HAND SPEC: ASTM B247 QQ-A-367	MIL-A-22771	B	C											
52419	AL 2014-T652 RINGS ROLLED SPEC: MIL-A-22771		B	C											
52813	AL 2017-O BAR COLD FINISHED SPEC: QQ-A-225/5E		B	U											
52809	AL 2017-O BAR DRAWN SPEC: QQ-A-225/5E		B	N											
30099	AL 2017-O BAR ROLLED SPEC: ASTM B211	QQ-A-225/5E	B	N	U		U	U		A		A	A		
52819	AL 2017-O ROD COLD FINISHED SPEC: QQ-A-225/5E		B	N											
52829	AL 2017-O ROD DRAWN SPEC: QQ-A-225/5E		B	N											
50549	AL 2017-O ROD ROLLED SPEC: ASTM B211	QQ-A-225/5E	B	N	U		U	U		A		A	A		
52826	AL 2017-O WIRE COLD FINISHED SPEC: QQ-A-225/5E		B	N											
52823	AL 2017-O WIRE DRAWN SPEC: QQ-A-225/5E		B	N											
50550	AL 2017-O WIRE ROLLED SPEC: ASTM B211	QQ-A-225/5E	B	N	U		U	U		A		A	A		
52814	AL 2017-T4 BAR COLD FINISHED SPEC: QQ-A-225/5E		B	C											
52810	AL 2017-T4 BAR DRAWN SPEC: QQ-A-225/5E		B	C											
50255	AL 2017-T4 BAR ROLLED SPEC: AMS 4118 QQ-A-225/5E	ASTM B211	B	C	A		A	A		A		A	A		
52820	AL 2017-T4 ROD COLD FINISHED SPEC: QQ-A-225/5E		B	C											
52830	AL 2017-T4 ROD DRAWN		B	C											

MSFC-HDBK-527 REV F 9999942 0004841 9

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50543	AL 2017-T4 ROD ROLLED SPEC: AMS 4118 QQ-A-225/5E	ASTM B211	B	C											
52827	AL 2017-T4 WIRE COLD FINISHED SPEC: QQ-A-225/5E		B	B											
52824	AL 2017-T4 WIRE DRAWN SPEC: QQ-A-225/5E		B	B											
50544	AL 2017-T4 WIRE ROLLED SPEC: AMS 4118 QQ-A-225/5E	ASTM B211	B	B											
52815	AL 2017-T42 BAR COLD FINISHED SPEC: QQ-A-225/5E		B	C											
52811	AL 2017-T42 BAR DRAWN SPEC: QQ-A-225/5E		B	C											
50254	AL 2017-T42 BAR ROLLED SPEC: ASTM B211	QQ-A-225/5E	B	C	A		A	A		A		A	A		
52821	AL 2017-T42 ROD COLD FINISHED SPEC: QQ-A-225/5E		B	C											
52817	AL 2017-T42 ROD DRAWN SPEC: QQ-A-225/5E		B	C											
50545	AL 2017-T42 ROD ROLLED SPEC: ASTM B211	QQ-A-225/5E	B	C	A		A	A		A		A	A		
52828	AL 2017-T42 WIRE COLD FINISHED SPEC: QQ-A-225/5E		B	B											
52825	AL 2017-T42 WIRE DRAWN SPEC: QQ-A-225/5E		B	B											
50546	AL 2017-T42 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/5E	B	B	A		A	A		A		A	A		
52816	AL 2017-T451 BAR COLD FINISHED SPEC: QQ-A-225/5E		B	C											
52812	AL 2017-T451 BAR DRAWN SPEC: QQ-A-225/5E		B	C											
50253	AL 2017-T451 BAR ROLLED SPEC: AMS 4110 QQ-A-225/5E	ASTM B211	B	C	A		A	A		A		A	A		

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52822	AL 2017-T451 ROD COLD FINISHED SPEC: QQ-A-225/5E		B	C											
52818	AL 2017-T451 ROD DRAWN SPEC: QQ-A-225/5E		B	C											
50547	AL 2017-T451 ROD ROLLED SPEC: AMS 4110 QQ-A-225/5E	ASTM B211	B	C	A		A	A		A		A	A		
52831	AL 2017-T451 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/5E	B	B	A		A	A		A		A	A		
51593	AL 2018-T61 FORGING DIE SPEC: AMS 4140	QQ-A-367H	B	U											
52458	AL 2024 PLATE ONE SIDE CLAD		B	N											
52457	AL 2024 SHEET ONE SIDE CLAD		B	N											
50551	AL 2024-F PLATE CLAD SPEC: QQ-A-250/5		B	N	A		A	A		A		A	A		
50265	AL 2024-F SHEET CLAD SPEC: QQ-A-250/5		B	N	A		A	A		A		A	A		
51134	AL 2024-H13 ROD RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430	B	B											
51130	AL 2024-H13 WIRE RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430	B	B											
51136	AL 2024-H23 ROD RIVET AND COLD HEADING SPEC: QQ-A-430		B	B											
51132	AL 2024-H23 WIRE RIVET AND COLD HEADING SPEC: QQ-A-430		B	B											
53029	AL 2024-O BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/6	B	N											
51112	AL 2024-O BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	N											
10744	AL 2024-O BAR ROLLED SPEC: ASTM B211	QQ-A-225/6	B	N	A		A	A		A		A	A		
51090	AL 2024-O PLATE SPEC: AMS 4035 QQ-A-250/4	ASTM B209	B	N	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004843 2

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52456	AL 2024-O PLATE 1 1/2% CLAD		B	N											
52460	AL 2024-O PLATE 1 1/2% ONE SIDE CLAD		B	N											
10408	AL 2024-O PLATE CLAD SPEC: AMS 4040 QQ-A-250/5	ASTM B209	B	U	A		A	A		A		A	A		
52884	AL 2024-O PLATE ONE SIDE CLAD SPEC: AMS 4077														
53032	AL 2024-O ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/6	B	N											
51148	AL 2024-O ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	N											
51133	AL 2024-O ROD RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430	B	N											
10525	AL 2024-O ROD ROLLED SPEC: ASTM B211	QQ-A-225/6	B	N	A		A	A		A		A	A		
51155	AL 2024-O SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	N											
30140	AL 2024-O SHEET SPEC: AMS 4035 QQ-A-250/4	ASTM B209	B	N	A		A	A		A		A	A		
52455	AL 2024-O SHEET 1 1/2% CLAD		B	N											
52459	AL 2024-O SHEET 1 1/2% ONE SIDE CLAD		B	N											
50581	AL 2024-O SHEET CLAD SPEC: AMS 4040 QQ-A-250/5	ASTM B209	B	N	A		A	A		A		A	A		
52883	AL 2024-O SHEET ONE SIDE CLAD SPEC: AMS 4077		B	N											
53030	AL 2024-O TUBE DRAWN SPEC: AMS 4087		B	N											
51127	AL 2024-O TUBE DRAWN SEAMLESS SPEC: AMS 4087 MIL-T-50777	ASTM B210 WW-T-700/3	B	N											
51117	AL 2024-O TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/3	ASTM B241	B	N											

MSFC-HDBK-527 REV F 9999942 0004844 4

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53031	AL 2024-O TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	N											
53033	AL 2024-O WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/6	B	N											
51109	AL 2024-O WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	N											
51129	AL 2024-O WIRE RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430	B	N											
50580	AL 2024-O WIRE ROLLED SPEC: ASTM B211	QQ-A-225/6	B	N	A		A	A		A		A	A		
30112	AL 2024-T3 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	C	A		A	A		A		A	A		
30108	AL 2024-T3 FASTENERS ONLY		B	C	A		A	A		A		A	A		
50556	AL 2024-T3 PLATE SPEC: QQ-A-250/4		B	C	A		A	A		A		A	A		
50555	AL 2024-T3 PLATE CLAD SPEC: QQ-A-250/5		B	C	A		A	A		A		A	A		
50552	AL 2024-T3 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	C											
51156	AL 2024-T3 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	C											
30111	AL 2024-T3 SHEET SPEC: AMS 4037 QQ-A-250/4	ASTM B209	B	B	A		A	A		A		A	A		
52494	AL 2024-T3 SHEET 1 1/2% CLAD		B	B											
50256	AL 2024-T3 SHEET CLAD SPEC: AMS 4041 QQ-A-250/5	ASTM B209	B	B	A		A	A		A		A	A		
52507	AL 2024-T3 SHEET ONE SIDE 1 1/2% CLAD		B	B											
52881	AL 2024-T3 SHEET ONE SIDE CLAD SPEC: AMS 4036		B	N											
53035	AL 2024-T3 TUBE DRAWN SPEC: AMS 4088		B	B											
50554	AL 2024-T3 TUBE DRAWN SEAMLESS SPEC: AMS 4086 ASTM B210	AMS 4088 MIL-T-50777	B	B											

MSFC-HDBK-527 REV F 9999942 0004845 6

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51118	AL 2024-T3 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/3	ASTM B241	B	B											
53034	AL 2024-T3 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
53036	AL 2024-T3 TUBE HYDRAULIC SPEC: AMS 4086		B	B											
50553	AL 2024-T3 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	B											
53037	AL 2024-T351 BAR COLD FINISHED SPEC: AMS 4119 QQ-A-225/6	ASTM B211	B	C											
51106	AL 2024-T351 BAR ROLLED SPEC: AMS 4119 QQ-A-225/6	ASTM B211	B	C											
50558	AL 2024-T351 PLATE SPEC: AMS 4037 QQ-A-250/4	ASTM B209	B	C	A		A	A		A		A	A		
52495	AL 2024-T351 PLATE 1 1/2% CLAD		B	C											
50557	AL 2024-T351 PLATE CLAD SPEC: AMS 4041 QQ-A-250/5	ASTM B209	B	C	A		A	A		A		A	A		
52508	AL 2024-T351 PLATE ONE SIDE 1 1/2% CLAD		B	C											
52882	AL 2024-T351 PLATE ONE SIDE CLAD SPEC: AMS 4036		B	C											
53038	AL 2024-T351 ROD COLD FINISHED SPEC: AMS 4119 QQ-A-225/6	ASTM B211	B	C											
51107	AL 2024-T351 ROD ROLLED SPEC: AMS 4119 QQ-A-225/6	ASTM B211	B	C											
30055	AL 2024-T351 SHEET SPEC: QQ-A-250/4		B	B	A		A	A		A		A	A		
50263	AL 2024-T351 SHEET CLAD SPEC: QQ-A-250/5		B	B	A		A	A		A		A	A		
51113	AL 2024-T3510 BAR EXTRUDED SPEC: AMS 4164 QQ-A-200/3	ASTM B221	B	C											

MSFC-HDBK-527 REV F 9999942 0004846 8

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51150	AL 2024-T3510 ROD EXTRUDED SPEC: AMS 4164 QQ-A-200/3	ASTM B221	B	C											
51157	AL 2024-T3510 SHAPES EXTRUDED SPEC: AMS 4164 QQ-A-200/3	ASTM B221	B	C											
51120	AL 2024-T3510 TUBE EXTRUDED SPEC: AMS 4164 ASTM B241	ASTM B221 QQ-A-200/3	B	B											
53040	AL 2024-T3510 TUBE EXTRUDED SEAMELSS SPEC: ASTM B241		B	B											
53039	AL 2024-T3510 TUBE ROUND EXTRUDED SPEC: AMS 4164		B	B											
53041	AL 2024-T3510 WIRE EXTRUDED SPEC: ASTM B221		B	B											
51114	AL 2024-T3511 BAR EXTRUDED SPEC: AMS 4165 QQ-A-200/3	ASTM B221	B	C											
51151	AL 2024-T3511 ROD EXTRUDED SPEC: AMS 4165 QQ-A-200/3	ASTM B221	B	C											
51158	AL 2024-T3511 SHAPES EXTRUDED SPEC: AMS 4165 QQ-A-200/3	ASTM B221	B	C											
51121	AL 2024-T3511 TUBE EXTRUDED SPEC: AMS 4165 ASTM B241	ASTM B221 QQ-A-200/3	B	B											
53042	AL 2024-T3511 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
53043	AL 2024-T3511 TUBE ROUND EXTRUDED SPEC: AMS 4165		B	B											
53044	AL 2024-T3511 WIRE EXTRUDED SPEC: ASTM B221		B	B											
50559	AL 2024-T36 PLATE CLAD SPEC: QQ-A-250/5		B	C	A		A	A		A		A	A		
50257	AL 2024-T36 SHEET CLAD SPEC: QQ-A-250/5		B	B	A		A	A		A		A	A		

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53045	AL 2024-T36 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/6	B	B											
51105	AL 2024-T36 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/6	B	B											
51092	AL 2024-T361 PLATE SPEC: AMS 4192 QQ-A-250/4	ASTM B209	B	C											
52496	AL 2024-T361 PLATE 1 1/2% CLAD		B	C											
51204	AL 2024-T361 PLATE CLAD SPEC: AMS 4194 QQ-A-250/5	ASTM B209	B	C											
52509	AL 2024-T361 PLATE ONE SIDE 1 1/2% CLAD		B	C											
51091	AL 2024-T361 SHEET SPEC: AMS 4192 QQ-A-250/4	ASTM B209	B	B											
52497	AL 2024-T361 SHEET 1 1/2% CLAD		B	B											
51203	AL 2024-T361 SHEET CLAD SPEC: AMS 4194 QQ-A-250/5	ASTM B209	B	B											
52510	AL 2024-T361 SHEET ONE SIDE 1 1/2% CLAD		B	B											
53046	AL 2024-T4 BAR COLD FINISHED SPEC: AMS 4120 QQ-A-225/6	ASTM B211	B	C											
51116	AL 2024-T4 BAR EXTRUDED SPEC: AMS 4152		B	C											
50267	AL 2024-T4 BAR ROLLED SPEC: AMS 4120 QQ-A-225/6	ASTM B211	B	C	A		A	A		A		A	A		
50266	AL 2024-T4 FASTENERS ONLY		B	C	A		A	A		A		A	A		
50564	AL 2024-T4 PLATE SPEC: AMS 4037		B	C	A		A	A		A		A	A		
50563	AL 2024-T4 PLATE CLAD		B	C	A		A	A		A		A	A		
53047	AL 2024-T4 ROD COLD FINISHED SPEC: AMS 4120 QQ-A-225/6	ASTM B211	B	C											

MSFC-HDBK-527 REV F 9999942 0004848 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZK RTG	HDZK TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51154	AL 2024-T4 ROD EXTRUDED SPEC: AMS 4152		B	C											
51135	AL 2024-T4 ROD RIVET AND COLD HEADING SPEC: ASTM B316		B	C											
50560	AL 2024-T4 ROD ROLLED SPEC: AMS 4120 QQ-A-225/6	ASTM B211	B	C	A		A	A		A		A	A		
51161	AL 2024-T4 SHAPES EXTRUDED SPEC: AMS 4152		B	C											
50268	AL 2024-T4 SHEET SPEC: ASTM B209	QQ-A-250/4	B	B	A		A	A		A		A	A		
50258	AL 2024-T4 SHEET CLAD SPEC: ASTM B209	QQ-A-250/5	B	B	A		A	A		A		A	A		
50562	AL 2024-T4 TUBE SPEC: QQ-A-200/3		B	B											
51126	AL 2024-T4 TUBE EXTRUDED SPEC: AMS 4152		B	B											
53048	AL 2024-T4 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/6	B	B											
51131	AL 2024-T4 WIRE RIVET AND COLD HEADING SPEC: ASTM B316		B	B											
50561	AL 2024-T4 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/6	B	B											
30071	AL 2024-T4/T3511 SPEC: QQ-A-200/3		B	C	A		A	A		A		A	A		
53050	AL 2024-T42 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/6	B	C											
51115	AL 2024-T42 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	C											
51101	AL 2024-T42 BAR ROLLED SPEC: ASTM B211	QQ-A-225/6	B	C											
51097	AL 2024-T42 PLATE SPEC: ASTM B209	QQ-A-250/4	B	C											
52498	AL 2024-T42 PLATE BOTH SIDES 1 1/2% CLAD		B	C											

MSFC-HDBK-527 REV F 9999942 0004849 3

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50565	AL 2024-T42 PLATE CLAD SPEC: ASTM B209	QQ-A-250/5	B	C	A		A	A		A		A	A		
52511	AL 2024-T42 PLATE ONE SIDE 1 1/2% CLAD		B	C											
53051	AL 2024-T42 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/6	B	C											
51152	AL 2024-T42 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	C											
51100	AL 2024-T42 ROD ROLLED SPEC: ASTM B211	QQ-A-225/6	B	C											
51159	AL 2024-T42 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	C											
51096	AL 2024-T42 SHEET SPEC: ASTM B209	QQ-A-250/4	B	B											
52499	AL 2024-T42 SHEET BOTH SIDES 1 1/2% CLAD		B	B											
50259	AL 2024-T42 SHEET CLAD SPEC: AMS 4087 QQ-A-250/5	ASTM B209	B	B	A		A	A		A		A	A		
52512	AL 2024-T42 SHEET ONE SIDE 1 1/2% CLAD		B	B											
51128	AL 2024-T42 TUBE DRAWN SEAMLESS SPEC: ASTM B210 WW-T-700/3	MIL-T-50777	B	B											
51122	AL 2024-T42 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/3	ASTM B241	B	B											
53049	AL 2024-T42 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
53052	AL 2024-T42 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/6	B	B											
51110	AL 2024-T42 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	B											
51099	AL 2024-T42 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/6	B	B											
50221	AL 2024-T6 BAR COLD FINISHED SPEC: AMS 4112 QQ-A-225/6	ASTM B211	B	B	A		A	A		A		A	A		

MSFC-HDBK-527 REV F ■ 9999942 0004850 T ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51098	AL 2024-T6 BAR ROLLED SPEC: AMS 4112 QQ-A-225/6	ASTM B211	B	B	A		A	A		A		A	A		
10411	AL 2024-T6 FORGING		B	C	A		A	A		A		A	A		
50567	AL 2024-T6 PLATE CLAD SPEC: QQ-A-250/5		B	B	A		A	A		A		A	A		
53053	AL 2024-T6 ROD COLD FINISHED SPEC: AMS 4112 QQ-A-225/6	ASTM B211	B	B	A		A	A		A		A	A		
10292	AL 2024-T6 ROD ROLLED SPEC: AMS 4112 QQ-A-225/6	ASTM B211	B	B	A	1000	A	A		A		A	A		
50260	AL 2024-T6 SHEET CLAD SPEC: QQ-A-250/5		B	A	A		A	A		A		A	A		
50566	AL 2024-T6 WIRE COLD FINISHED SPEC: AMS 4112 QQ-A-225/6	ASTM B211	B	B	A		A	A		A		A	A		
53054	AL 2024-T6 WIRE ROLLED SPEC: AMS 4112 QQ-A-225/6	ASTM B211	B	A	A		A	A		A		A	A		
53055	AL 2024-T62 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/6	B	B											
51104	AL 2024-T62 BAR ROLLED SPEC: ASTM B211	QQ-A-225/6	B	B											
50570	AL 2024-T62 PLATE SPEC: ASTM B209	QQ-A-250/4	B	C	A		A	A		A		A	A		
52500	AL 2024-T62 PLATE 1 1/2% CLAD		B	C											
51206	AL 2024-T62 PLATE CLAD SPEC: ASTM B209	QQ-A-250/5	B	C											
52513	AL 2024-T62 PLATE ONE SIDE 1 1/2% CLAD		B	C											
53056	AL 2024-T62 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/6	B	B											
51103	AL 2024-T62 ROD ROLLED SPEC: ASTM B211	QQ-A-225/6	B	B											
10210	AL 2024-T62 SHEET SPEC: ASTM B209	QQ-A-250/4	B	A	A	1000	A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004851 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52501	AL 2024-T62 SHEET 1 1/2% CLAD		B	A											
51205	AL 2024-T62 SHEET CLAD SPEC: ASTM B209	QQ-A-250/5	B	A											
52514	AL 2024-T62 SHEET ONE SIDE 1 1/2% CLAD		B	A											
10216	AL 2024-T62 TUBE SPEC: WW-T-700/3		B	A	A	1000	A	A		A		A	A		
53057	AL 2024-T62 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/6	B	A											
51102	AL 2024-T62 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/6	B	A											
10291	AL 2024-T6X BAR EXTRUDED SPEC: QQ-A-200/3		B	B	A	1000	A	A		A		A	A		
50568	AL 2024-T6X ROD EXTRUDED SPEC: QQ-A-200/3		B	B	A		A	A		A		A	A		
50569	AL 2024-T6X WIRE EXTRUDED SPEC: QQ-A-200/3		B	A	A		A	A		A		A	A		
51095	AL 2024-T72 SHEET SPEC: ASTM B209	QQ-A-250/4	B	A											
52502	AL 2024-T72 SHEET 1 1/2% CLAD		B	A											
51207	AL 2024-T72 SHEET CLAD SPEC: ASTM B209	QQ-A-250/5	B	A											
52515	AL 2024-T72 SHEET ONE SIDE 1 1/2% CLAD		B	A											
50117	AL 2024-T8 FORGING		B	C	A		A	A		A		U	U		
53058	AL 2024-T81 BAR EXTRUDED SPEC: ASTM B221		B	A	A		A	A		A		A	A		
10260	AL 2024-T81 FOIL		B	A	A		A	A		A		A	A		
50575	AL 2024-T81 PLATE SPEC: QQ-A-250/4		B	B	A		A	A		A		A	A		
50092	AL 2024-T81 PLATE CLAD SPEC: QQ-A-250/5		B	B	A		A	A		A		A	A		
53059	AL 2024-T81 ROD EXTRUDED SPEC: ASTM B221		B	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004852 3

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53060	AL 2024-T81 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	A	A		A	A		A		A	A		
10750	AL 2024-T81 SHEET SPEC: ASTM B209	QQ-A-250/4	B	A	A		A	A		A		A	A		
52503	AL 2024-T81 SHEET 1 1/2% CLAD		B	A	A		A	A		A		A	A		
50574	AL 2024-T81 SHEET CLAD SPEC: ASTM B209	QQ-A-250/5	B	A	A		A	A		A		A	A		
52516	AL 2024-T81 SHEET ONE SIDE 1 1/2% CLAD		B	A											
10005	AL 2024-T81 TUBE DRAWN SEAMLESS SPEC: WW-T-700/3		B	A			A	A		A		A	A		
51123	AL 2024-T81 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/3	ASTM B241	B	A	A		A	A		A		A	A		
53062	AL 2024-T81 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A	A		A	A		A		A	A		
51111	AL 2024-T81 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	A	A		A	A		A		A	A		
50222	AL 2024-T851 BAR														
53064	AL 2024-T851 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/6	B	A											
10508	AL 2024-T851 BAR ROLLED SPEC: ASTM B211	QQ-A-225/6	B	A	A		A	A		A		A	A		
50973	AL 2024-T851 PLATE SPEC: ASTM B209	QQ-A-250/4	B	B											
52504	AL 2024-T851 PLATE 1 1/2% CLAD		B	B											
50264	AL 2024-T851 PLATE CLAD SPEC: ASTM B209	QQ-A-250/5	B	B	A		A	A		A		A	A		
52517	AL 2024-T851 PLATE ONE SIDE 1 1/2% ONE		B	B											
53063	AL 2024-T851 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/6	B	A	A		A	A		A		A	A		
51108	AL 2024-T851 ROD ROLLED SPEC: ASTM B211	QQ-A-225/6	B	A	A		A	A		A		A	A		
50576	AL 2024-T851 SHEET CLAD SPEC: QQ-A-250/5		B	A	A		A			A		A	A		

MSFC-HDBK-527 REV F 9999942 0004853 5

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10420	AL 2024-T8510 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	B	A	1000	A	A		A		A	A		
50577	AL 2024-T8510 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	B	A	1000	A	A		A		A	A		
53065	AL 2024-T8510 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	B	A		A	A		A		A	A		
51124	AL 2024-T8510 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	A	A		A	A		A		A	A		
53068	AL 2024-T8510 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A	A		A	A		A		A	A		
50578	AL 2024-T8510 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	A	A	1000	A	A		A		A	A		
53067	AL 2024-T8511 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	B											
51153	AL 2024-T8511 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	B											
51160	AL 2024-T8511 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	B											
51125	AL 2024-T8511 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/3	B	A											
53069	AL 2024-T8511 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
53066	AL 2024-T8511 WIRE EXTRUDED SPEC: ASTM B221		B	A											
50262	AL 2024-T86 PLATE CLAD SPEC: QQ-A-250/5		B	B	A		A	A		A		A	A		
50579	AL 2024-T86 SHEET CLAD SPEC: QQ-A-250/5		B	A	A		A	A		A		A	A		
51094	AL 2024-T861 PLATE SPEC: AMS 4193 QQ-A-250/4	ASTM B209	B	B											
52505	AL 2024-T861 PLATE 1 1/2% CLAD		B	B											
51209	AL 2024-T861 PLATE CLAD SPEC: AMS 4195 QQ-A-250/5	ASTM B209	B	B											

MSFC-HDBK-527 REV F 9999942 0004854 7

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52518	AL 2024-T861 PLATE ONE SIDE 1 1/2% CLAD		B	B											
51093	AL 2024-T861 SHEET SPEC: AMS 4193 QQ-A-250/4	ASTM B209	B	A											
52506	AL 2024-T861 SHEET 1 1/2% CLAD		B	A											
51208	AL 2024-T861 SHEET CLAD SPEC: AMS 4195 QQ-A-250/5	ASTM B209	B	A											
52519	AL 2024-T861 SHEET ONE SIDE 1 1/2% CLAD		B	A											
10004	AL 2024-T8X BAR EXTRUDED SPEC: QQ-A-200/3		B	B			A	A		A		A	A		
50573	AL 2024-T8X PLATE SPEC: MB0170-078	QQ-A-250/4	B	B	A		A	A		A		A	A		
50571	AL 2024-T8X ROD EXTRUDED		B	B	A		A	A		A		A	A		
10205	AL 2024-T8X SHEET SPEC: MB0170-078	QQ-A-250/4	B	A	A		A	A		A		A	A		
50572	AL 2024-T8X WIRE EXTRUDED		B	A	A		A	A		A		A	A		
51140	AL 2025-F FORGING DIE SPEC: AMS 4130		B	U											
51142	AL 2025-F FORGING STOCK SPEC: AMS 4130		B	U											
52619	AL 2025-T6 FORGING SPEC: AMS 4130		B	U											
51139	AL 2025-T6 FORGING DIE SPEC: QQ-A-367		B	U											
51141	AL 2025-T6 FORGING STOCK SPEC: QQ-A-367		B	U											
51173	AL 2036-T4 SHEET		B	B											
50977	AL 2048-T851 PLATE		B	B											
53070	AL 2117-H13 RIVET AND ROD COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A	A		A	A		A		A	A		
10224	AL 2117-H13 ROD SPEC: ASTM B316	QQ-A-430	B	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004855 9

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50582	AL 2117-H13 WIRE RIVET AND COLD HEADING SPEC: QQ-A-430	B	A	A		A	A		A		A	A		
51769	AL 2117-H15 ROD RIVET AND COLD HEADING SPEC: ASTM B316 QQ-A-430C	B	A											
51768	AL 2117-H15 WIRE RIVET AND COLD HEADING SPEC: ASTM B316 QQ-A-430C	B	A											
51772	AL 2117-H23 ROD RIVET AND COLD HEADING SPEC: QQ-A-430C	B	A											
51771	AL 2117-H25 ROD RIVET AND COLD HEADING SPEC: QQ-A-430C	B	A											
51770	AL 2117-H25 WIRE RIVET AND COLD HEADING SPEC: QQ-A-430C	B	A											
51767	AL 2117-O ROD RIVET AND COLD HEADING SPEC: ASTM B316 QQ-A-430C	B	N											
51766	AL 2117-O WIRE RIVET AND COLD HEADING SPEC: ASTM B316 QQ-A-430C	B	N											
53071	AL 2117-T4 RIVET AND ROD COLD HEADING SPEC: ASTM B316 QQ-A-430C	B	A	A		A	A		A		A	A		
10335	AL 2117-T4 ROD SPEC: QQ-A-430	B	A	A		A	A		A		A	A		
50583	AL 2117-T4 WIRE RIVET AND COLD HEADING SPEC: ASTM B316 QQ-A-430C	B	A	A		A	A		A		A	A		
10006	AL 2124-T851 PLATE SPEC: AMS 4101 ASTM B209 QQ-A-250/29	B	B	A	1000	A	A		A		A	A		
52492	AL 218-F CASTINGS DIE	B	A											
52489	AL 220-T4 CASTINGS SAND	B	C											
51190	AL 2218-F FORGING DIE SPEC: AMS 4142 QQ-A-367H	B	A											
51191	AL 2218-T61 FORGING DIE SPEC: QQ-A-367H	B	A											
51192	AL 2218-T72 FORGING DIE SPEC: QQ-A-367H	B	A											
51084	AL 2219-H13 ROD RIVET AND COLD HEADING SPEC: ASTM B316 QQ-A-430C	B	B											

MSFC-HDBK-527 REV F 9999942 0004856 0

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51082	AL 2219-H13 WIRE RIVET AND COLD HEADING SPEC: ASTM B316 QQ-A-430C	B	B											
51089	AL 2219-H23 ROD RIVET AND COLD HEADING SPEC: QQ-A-430C	B	B											
51087	AL 2219-H23 WIRE RIVET AND COLD HEADING SPEC: QQ-A-430C	B	B											
51052	AL 2219-O BAR EXTRUDED SPEC: ASTM B221	B	N											
51047	AL 2219-O PLATE SPEC: AMS 4031 ASTM B209 QQ-A-250/30	B	N											
53083	AL 2219-O PLATE CLAD SPEC: AMS 4096 ASTM B209													
51051	AL 2219-O ROD EXTRUDED SPEC: ASTM B221	B	N											
51088	AL 2219-O ROD RIVET AND COLD HEADING SPEC: QQ-A-430C	B	N											
51053	AL 2219-O SHAPES EXTRUDED SPEC: ASTM B221	B	N											
51046	AL 2219-O SHEET SPEC: AMS 4031 ASTM B209 QQ-A-250/30	B	N											
51054	AL 2219-O TUBE EXTRUDED SPEC: ASTM B221	B	N											
52605	AL 2219-O TUBE EXTRUDED SEAMLESS SPEC: ASTM B241	B	N											
51050	AL 2219-O WIRE EXTRUDED SPEC: ASTM B221	B	N											
51086	AL 2219-O WIRE RIVET AND COLD HEADING SPEC: QQ-A-430C	B	N											
51057	AL 2219-T31 BAR EXTRUDED SPEC: ASTM B221	B	C											
50584	AL 2219-T31 PLATE SPEC: QQ-A-250/30	B	C	A		A	A		A		U	U		
51056	AL 2219-T31 ROD EXTRUDED SPEC: ASTM B221	B	C											

MSFC-HDBK-527 REV F 9999942 0004857 2

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51058	AL 2219-T31 SHAPES EXTRUDED SPEC: ASTM B221		B	C											
50079	AL 2219-T31 SHEET SPEC: ASTM B209	QQ-A-250/30	B	B	A		A	A		A		U	U		
51059	AL 2219-T31 TUBE EXTRUDED SPEC: ASTM B221		B	B											
52606	AL 2219-T31 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
51055	AL 2219-T31 WIRE EXTRUDED SPEC: ASTM B221		B	B											
50076	AL 2219-T351 PLATE SPEC: ASTM B209	QQ-A-250/30	B	B	A		A	A		A		U	U		
10708	AL 2219-T351 SHEET SPEC: QQ-A-250/30		B	B	A		A	A		A		A	A		
51062	AL 2219-T3510 BAR EXTRUDED SPEC: ASTM B221		B	C											
51061	AL 2219-T3510 ROD EXTRUDED SPEC: ASTM B221		B	C											
51063	AL 2219-T3510 SHAPES EXTRUDED SPEC: ASTM B221		B	C											
51064	AL 2219-T3510 TUBE EXTRUDED SPEC: ASTM B221		B	B											
52607	AL 2219-T3510 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
51060	AL 2219-T3510 WIRE EXTRUDED SPEC: ASTM B221		B	B											
50088	AL 2219-T3511 BAR EXTRUDED SPEC: AMS 4163	ASTM B221	B	C	A		A	A		A		U	U		
50585	AL 2219-T3511 ROD EXTRUDED SPEC: AMS 4163	ASTM B221	B	C	A		A	A		A		U	U		
51066	AL 2219-T3511 SHAPES EXTRUDED SPEC: AMS 4163	ASTM B221	B	C	A		A	A		A		U	U		
51067	AL 2219-T3511 TUBE EXTRUDED SPEC: AMS 4163	ASTM B221	B	B	A		A	A		A		U	A		

MSFC-HDBK-527 REV F 9999942 0004858 4

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZK RTG	HDZK TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52608	AL 2219-T3511 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B	A		A	A		A		U	U		
50586	AL 2219-T3511 WIRE EXTRUDED SPEC: ASTM B221		B	B	A		A	A		A		U	U		
50073	AL 2219-T352 FORGING SPEC: QQ-A-367		B	C	A		A	A		A		U	U		
50587	AL 2219-T37 PLATE SPEC: ASTM B209	QQ-A-250/30	B	C	A		A	A		A		U	U		
50072	AL 2219-T37 SHEET SPEC: ASTM B209	QQ-A-250/30	B	B	A		A	A		A		U	U		
50588	AL 2219-T42 PLATE SPEC: QQ-A-250/30		B	C	A		A	A		A		U	U		
10466	AL 2219-T42 RIVETS MANF: ARMCO		B	B	A		A	A		A		A	A		
50080	AL 2219-T42 SHEET SPEC: QQ-A-250/30		B	B	A		A	A		A		U	U		
53072	AL 2219-T6 FORGING SPEC: ASTM B247	QQ-A-367H	B	A	A		A	A		A		A	A		
50590	AL 2219-T6 FORGING DIE SPEC: AMS 4143 MIL-A-22771D	ASTM B247 QQ-A-367H	B	A	A		A	A		A		A	A		
10014	AL 2219-T6 FORGING HAND SPEC: AMS 4143 MIL-A-22771D	ASTM B247 QQ-A-367H	B	A	A		A	A		A		A	A		
51081	AL 2219-T6 RINGS ROLLED SPEC: MIL-A-22771D		B	A											
51085	AL 2219-T6 ROD RIVET AND COLD HEADING SPEC: ASTM B316		B	A											
51083	AL 2219-T6 WIRE RIVET AND COLD HEADING SPEC: ASTM B316		B	A											
10036	AL 2219-T62 BAR EXTRUDED SPEC: ASTM B221		B	A	A		A	A		A		A	A		
50589	AL 2219-T62 PLATE SPEC: ASTM B209 QQ-A-250/30	MB0170-078	B	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004859 6

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52603	AL 2219-T62 ROD EXTRUDED SPEC: ASTM B221		B	A	A		A	A		A		A	A		
52604	AL 2219-T62 SHAPES EXTRUDED SPEC: ASTM B221		B	A	A		A	A		A		A	A		
10015	AL 2219-T62 SHEET SPEC: ASTM B209 QQ-A-250/30	MB0170-078	B	A	A		A	A		A		A	A		
10412	AL 2219-T62 TUBE SPEC: ASTM B221	ASTM B241	B	A	A		A	A		A		A	A		
52610	AL 2219-T62 TUBE EXTRUDED SPEC: ASTM B221		B	A	A		A	A		A		A	A		
52612	AL 2219-T62 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A	A		A	A		A		A	A		
52602	AL 2219-T62 WIRE EXTRUDED SPEC: ASTM B221		B	A	A		A	A		A		A	A		
51070	AL 2219-T81 BAR EXTRUDED SPEC: ASTM B221		B	A											
51069	AL 2219-T81 ROD EXTRUDED SPEC: ASTM B221		B	A											
51071	AL 2219-T81 SHAPES EXTRUDED SPEC: ASTM B221		B	A											
10111	AL 2219-T81 SHEET SPEC: ASTM B209 QQ-A-250/30	MB0170-078	B	A	A		A	A		A		A	A		
50517	AL 2219-T81 TUBE SPEC: ASTM B221	ASTM B241	B	A			A	A		A		A	A		
52611	AL 2219-T81 TUBE EXTRUDED SPEC: ASTM B221		B	A											
52613	AL 2219-T81 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
51068	AL 2219-T81 WIRE EXTRUDED SPEC: ASTM B221		B	A											
52600	AL 2219-T851 BAR COLD FINISHED SPEC: ASTM B211		B	A											
51048	AL 2219-T851 BAR ROLLED SPEC: ASTM B211		B	A											

MSFC-HDBK-527 REV F 9999942 0004860 2

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50082	AL 2219-T851 PLATE SPEC: ASTM B209	QQ-A-250/30	B	A	A		A	A		A		A	A		
52601	AL 2219-T851 ROD COLD FINISHED SPEC: ASTM B211		B	A											
51049	AL 2219-T851 ROD ROLLED SPEC: ASTM B211		B	A											
50592	AL 2219-T851 SHEET SPEC: QQ-A-250/30		B	A	A		A	A		A		A	A		
51074	AL 2219-T8510 BAR EXTRUDED SPEC: ASTM B221		B	A											
51073	AL 2219-T8510 ROD EXTRUDED SPEC: ASTM B221		B	A											
51075	AL 2219-T8510 SHAPES EXTRUDED SPEC: ASTM B221		B	A											
51076	AL 2219-T8510 TUBE EXTRUDED SPEC: ASTM B221		B	A											
52609	AL 2219-T8510 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
51072	AL 2219-T8510 WIRE EXTRUDED SPEC: ASTM B221		B	A											
10013	AL 2219-T8511 BAR EXTRUDED SPEC: AMS 4162	ASTM B221	B	A	A		A	A		A		A	A		
50593	AL 2219-T8511 ROD EXTRUDED SPEC: AMS 4162	ASTM B221	B	A	A		A	A		A		A	A		
50594	AL 2219-T8511 SHAPES EXTRUDED SPEC: AMS 4162	ASTM B221	B	A	A		A	A		A		A	A		
51079	AL 2219-T8511 TUBE EXTRUDED SPEC: AMS 4162	ASTM B221	B	A	A		A	A		A		A	A		
51080	AL 2219-T8511 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A	A		A	A		A		A	A		
51077	AL 2219-T8511 WIRE EXTRUDED SPEC: ASTM B221		B	A	A		A	A		A		A	A		
30106	AL 2219-T852 FORGING SPEC: ASTM B247 QQ-A-367	MIL-A-22771	B	A	A		A	A		A		A	A		

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10007	AL 2219-T852 FORGING HAND SPEC: AMS 4144 MB0170-092 QQ-A-367H	ASTM B247 MIL-A-22771D	B	A	A		A	A		A		A	A		
50595	AL 2219-T87 PLATE SPEC: ASTM B209	QQ-A-250/30	B	A	A		A	A		A		A	A		
50081	AL 2219-T87 SHEET SPEC: ASTM B209	QQ-A-250/30	B	A	A		A	A		A		A	A		
50591	AL 2219-T8X PLATE SPEC: MB0170-078	QQ-A-250/30	B	A	A		A	A		A		A	A		
51812	AL 2319 ELECTRODES WELDING SPEC: MIL-E-16053	QQ-R-566	B	A											
51811	AL 2319 ROD WELDING SPEC: QQ-R-566		B	A											
51682	AL 2319-F ROD WELDING SPEC: AMS 4191		B	A											
51681	AL 2319-F WIRE WELDING SPEC: AMS 4191		B	A											
51683	AL 2319-T351 ELECTRODES WELDING SPEC: MIL-E-16053L		B	A											
50596	AL 2419-T8XX PLATE SPEC: MB0170-078	MB0170-083	B	A			A	A		A		A	A		
10273	AL 2419-T8XX SHEET SPEC: MB0170-083	MB0170-078	B	A			A	A		A		A	A		
52484	AL 2420-T77 SAND CASTING (WAS 142) SPEC: AMS 4222		B	C											
51143	AL 2618-F FORGING DIE SPEC: MIL-A-22771D		B	N											
51144	AL 2618-F FORGING HAND SPEC: MIL-A-22771D		B	N											
51145	AL 2618-F RINGS ROLLED SPEC: MIL-A-22771D		B	N											
51146	AL 2618-T61 FORGING DIE SPEC: AMS 4132C QQ-A-367H	MIL-A-22771D	B	C											

MSFC-HDBK-527 REV F ■ 9999942 0004862 6 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51147	AL 2618-T61 FORGING HAND SPEC: AMS 4132C QQ-A-367H	MIL-A-22771D	B	C											
51166	AL 2618-T61 FORGING STOCK SPEC: AMS 4132C		B	C											
53025	AL 2618-T61 ROLLED RINGS SPEC: AMS 4132C	MIL-A-22771D	B	C											
52486	AL 2950-T6 SAND CASTING (WAS 195) SPEC: AMS 4231		B	C											
10659	AL 3003 1-SIDE CLAD W/AL 4343 MANF: FOR BRAZING SPEC: AMS 4063		B	A	A		A	A		A		A	A		
50368	AL 3003 CLAD W/AL 4343 MANF: FOR BRAZING SPEC: AMS 4064		B	A	A		A	A		A		A	A		
50601	AL 3003 FOIL SPEC: AMS 4010		B	A											
50297	AL 3003 SHEET CLAD		B	A	U		U	A		A		U	U		
50599	AL 3003 STRIP SPEC: QQ-A-250/2		B	A											
53073	AL 3003 TUBE WELDED CLAD SPEC: ASTM B547		B	A											
52984	AL 3003-H112 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/2C	B	A											
52988	AL 3003-H112 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/1D	B	A											
50130	AL 3003-H112 BAR ROLLED SPEC: ASTM B211	QQ-A-225/2C	B	A	A		A	A		A		U	U		
53021	AL 3003-H112 FORGING DIE SPEC: ASTM B247		B	A											
52993	AL 3003-H112 PIPE SPEC: ASTM B241	MIL-P-25995	B	A											
52967	AL 3003-H112 PLATE SPEC: ASTM B209	QQ-A-250/2D	B	A											
51617	AL 3003-H112 PLATE CLAD SPEC: ASTM B209		B	A											

MSFC-HDBK-527 REV F 9999942 0004863 8

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52983	AL 3003-H112 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/2C	B	A											
52987	AL 3003-H112 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/1D	B	A											
50597	AL 3003-H112 ROD ROLLED SPEC: ASTM B211	QQ-A-225/2C	B	A	A		A	A		A		U	U		
52989	AL 3003-H112 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/1D	B	A											
52990	AL 3003-H112 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/1D	B	A											
51623	AL 3003-H112 TUBE EXTRUDED CLAD SPEC: ASTM B221		B	A											
52992	AL 3003-H112 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
52873	AL 3003-H112 TUBE EXTRUDED SEAMLESS CLAD SPEC: ASTM B241		B	A											
52995	AL 3003-H112 TUBE ROUND EXTRUDED SPEC: ASTM B491		B	A											
53014	AL 3003-H112 TUBE WELDED SPEC: ASTM B547		B	A											
51629	AL 3003-H112 TUBE WELDED CLAD SPEC: ASTM B547		B	A											
52982	AL 3003-H112 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/2C	B	A											
52986	AL 3003-H112 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/1D	B	A											
52981	AL 3003-H112 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/2C	B	A	A		A	A		A		U			
53001	AL 3003-H113 TUBE DRAWN SPEC: ASTM B483		B	A											
53007	AL 3003-H113 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/2	B	A											
51621	AL 3003-H113 TUBE DRAWN SEAMLESS CLAD SPEC: ASTM B210		B	A											

MSFC-HDBK-527 REV F ■ 9999942 0004864 T ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52962	AL 3003-H12 PLATE SPEC: ASTM B209	QQ-A-250/2D	B	A											
51612	AL 3003-H12 PLATE CLAD SPEC: ASTM B209		B	A											
52961	AL 3003-H12 SHEET SPEC: ASTM B209	QQ-A-250/2D	B	A											
51611	AL 3003-H12 SHEET CLAD SPEC: ASTM B209		B	A											
52997	AL 3003-H12 TUBE DRAWN SPEC: ASTM B483		B	A											
53003	AL 3003-H12 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/2	B	A											
53011	AL 3003-H12 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
51627	AL 3003-H12 TUBE WELDED CLAD SPEC: ASTM B547		B	A											
52974	AL 3003-H12 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/2C	B	A											
52973	AL 3003-H12 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/2C	B	A											
52964	AL 3003-H14 PLATE SPEC: AMS 4008 QQ-A-250/2D	ASTM B209	B	A											
51614	AL 3003-H14 PLATE CLAD SPEC: ASTM B209		B	A											
53020	AL 3003-H14 RIVET AND ROD COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											
53019	AL 3003-H14 RIVET AND WIRE COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											
52963	AL 3003-H14 SHEET SPEC: AMS 4008 QQ-A-250/2D	ASTM B209	B	A											
51613	AL 3003-H14 SHEET CLAD SPEC: ASTM B209		B	A											
53008	AL 3003-H14 TUBE CONDENSER SPEC: ASTM B234		B	A											

MSFC-HDBK-527 REV F 9999942 0004865 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51624	AL 3003-H14 TUBE CONDENSER CLAD SPEC: ASTM B234		B	A											
52998	AL 3003-H14 TUBE DRAWN SPEC: ASTM B483		B	A											
53004	AL 3003-H14 TUBE DRAWN SEAMLESS SPEC: AMS 4067 WW-T-700/2	ASTM B210	B	A											
51619	AL 3003-H14 TUBE DRAWN SEAMLESS CLAD SPEC: ASTM B210		B	A											
51628	AL 3003-H14 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
52976	AL 3003-H14 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/2C	B	A											
52975	AL 3003-H14 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/2C	B	A											
52965	AL 3003-H16 SHEET SPEC: ASTM B209	QQ-A-250/2D	B	A											
51615	AL 3003-H16 SHEET CLAD SPEC: ASTM B209		B	A											
52999	AL 3003-H16 TUBE DRAWN SPEC: ASTM B483		B	A											
53005	AL 3003-H16 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/2	B	A											
53012	AL 3003-H16 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
52978	AL 3003-H16 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/2C	B	A											
52977	AL 3003-H16 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/2C	B	A											
52994	AL 3003-H18 PIPE SPEC: ASTM B241	MIL-P-25995	B	A											
52966	AL 3003-H18 SHEET SPEC: ASTM B209	QQ-A-250/2D	B	A											
51616	AL 3003-H18 SHEET CLAD SPEC: ASTM B209		B	A											

MSFC-HDBK-527 REV F 9999942 0004866 3

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53000	AL 3003-H18 TUBE DRAWN SPEC: ASTM B483		B	A											
53006	AL 3003-H18 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/2	B	A											
51620	AL 3003-H18 TUBE DRAWN SEAMLESS CLAD SPEC: ASTM B210		B	A											
53013	AL 3003-H18 TUBE WELDED SPEC: ASTM B313		B	A											
52980	AL 3003-H18 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/2C	B	A											
52979	AL 3003-H18 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/2C	B	A											
53023	AL 3003-H24 RIVET AND ROD COLD HEADING SPEC: QQ-A-430C		B	A											
53022	AL 3003-H24 RIVET AND WIRE COLD HEADING SPEC: QQ-A-430C		B	A											
53009	AL 3003-H25 TUBE CONDENSER SPEC: ASTM B234		B	A											
51625	AL 3003-H25 TUBE CONDENSER CLAD SPEC: ASTM B234		B	A											
52972	AL 3003-O BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/2C	B	A											
50602	AL 3003-O BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/1D	B	A	A		A	A		A		U	U		
52971	AL 3003-O BAR ROLLED SPEC: ASTM B211	QQ-A-225/2C	B	A											
50600	AL 3003-O PLATE SPEC: AMS 4006 QQ-A-250/2D	ASTM B209	B	A	A		A	A		A		A	A		
51610	AL 3003-O PLATE CLAD SPEC: ASTM B209		B	A											
53018	AL 3003-O RIVET AND ROD COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											
53017	AL 3003-O RIVET AND WIRE COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											

MSFC-HDBK-527 REV F 9999942 0004867 5

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52970	AL 3003-O ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/2C	B	A											
10385	AL 3003-O ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/1D	B	A	A		A	A		A		U	U		
52969	AL 3003-O ROD ROLLED SPEC: ASTM B211	QQ-A-225/2C	B	A											
52985	AL 3003-O SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/1D	B	A											
10282	AL 3003-O SHEET SPEC: AMS 4006 QQ-A-250/2D	ASTM B209	B	A	A	1000	A	A		A		U	U		
51609	AL 3003-O SHEET CLAD SPEC: ASTM B209		B	A											
52996	AL 3003-O TUBE DRAWN SPEC: ASTM B483		B	A											
53002	AL 3003-O TUBE DRAWN SEAMLESS SPEC: AMS 4065 WW-T-700/2	ASTM B210	B	A											
51618	AL 3003-O TUBE DRAWN SEAMLESS CLAD SPEC: ASTM B210		B	A											
10437	AL 3003-O TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/1D	B	A	A		A	A		A		U	U		
51622	AL 3003-O TUBE EXTRUDED CLAD SPEC: ASTM B221		B	A											
52991	AL 3003-O TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
52872	AL 3003-O TUBE EXTRUDED SEAMLESS CLAD SPEC: ASTM B241		B	A											
53010	AL 3003-O TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
51626	AL 3003-O TUBE WELDED CLAD SPEC: ASTM B547		B	A											
52968	AL 3003-O WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/2C	B	A											
50603	AL 3003-O WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/1D	B	A	A		A	A		A		U	U		

MSFC-HDBK-527 REV F 9999942 0004868 7

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50598	AL 3003-O WIRE ROLLED SPEC: ASTM B211	QQ-A-225/2C	B	A											
51602	AL 3004-H112 PLATE SPEC: ASTM B209		B	A											
51760	AL 3004-H112 PLATE CLAD SPEC: ASTM B209		B	A											
51597	AL 3004-H32 PLATE SPEC: ASTM B209		B	A											
51758	AL 3004-H32 PLATE CLAD SPEC: ASTM B209		B	A											
51596	AL 3004-H32 SHEET SPEC: ASTM B209		B	A											
51753	AL 3004-H32 SHEET CLAD SPEC: ASTM B209		B	A											
52875	AL 3004-H32 TUBE ROUND CLAD SPEC: ASTM B547		B	A											
51605	AL 3004-H32 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
51762	AL 3004-H32 TUBE WELDED CLAD SPEC: ASTM B313		B	A											
51599	AL 3004-H34 PLATE SPEC: ASTM B209		B	A											
51759	AL 3004-H34 PLATE CLAD SPEC: ASTM B209		B	A											
51598	AL 3004-H34 SHEET SPEC: ASTM B209		B	A											
51754	AL 3004-H34 SHEET CLAD SPEC: ASTM B209		B	A											
52876	AL 3004-H34 TUBE ROUND CLAD SPEC: ASTM B547		B	A											
51606	AL 3004-H34 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
51763	AL 3004-H34 TUBE WELDED CLAD SPEC: ASTM B313		B	A											

MSFC-HDBK-527 REV F 9999942 0004869 9

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51600	AL 3004-H36 SHEET SPEC: ASTM B209		B	A											
51755	AL 3004-H36 SHEET CLAD SPEC: ASTM B209		B	A											
52877	AL 3004-H36 TUBE ROUND CLAD SPEC: ASTM B547		B	A											
51607	AL 3004-H36 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
51764	AL 3004-H36 TUBE WELDED CLAD SPEC: ASTM B313		B	A											
51601	AL 3004-H38 SHEET SPEC: ASTM B209		B	A											
51756	AL 3004-H38 SHEET CLAD SPEC: ASTM B209		B	A											
51608	AL 3004-H38 TUBE WELDED SPEC: ASTM B313		B	A											
51765	AL 3004-H38 TUBE WELDED CLAD SPEC: ASTM B313		B	A											
51595	AL 3004-O PLATE SPEC: ASTM B209		B	A											
51757	AL 3004-O PLATE CLAD SPEC: ASTM B209		B	A											
51594	AL 3004-O SHEET SPEC: ASTM B209		B	A											
51752	AL 3004-O SHEET CLAD SPEC: ASTM B209		B	A											
51603	AL 3004-O TUBE EXTRUDED SPEC: ASTM B221		B	A											
52874	AL 3004-O TUBE ROUND CLAD SPEC: ASTM B547		B	A											
51604	AL 3004-O TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
51761	AL 3004-O TUBE WELDED CLAD SPEC: ASTM B313		B	A											

MSFC-HDBK-527 REV F 9999942 0004870 5

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51709	AL 3005-H12 SHEET SPEC: ASTM B209	B	A											
51710	AL 3005-H14 SHEET SPEC: ASTM B209	B	A											
51711	AL 3005-H16 SHEET SPEC: ASTM B209	B	A											
51712	AL 3005-H18 SHEET SPEC: ASTM B209	B	A											
51713	AL 3005-H19 SHEET SPEC: ASTM B209	B	A											
51714	AL 3005-H26 SHEET SPEC: ASTM B209	B	A											
51715	AL 3005-H28 SHEET SPEC: ASTM B209	B	A											
51708	AL 3005-O SHEET SPEC: ASTM B209	B	A											
51703	AL 3105-H12 SHEET SPEC: ASTM B209	B	A											
51704	AL 3105-H14 SHEET SPEC: ASTM B209	B	A											
51705	AL 3105-H16 SHEET SPEC: ASTM B209	B	A											
51706	AL 3105-H18 SHEET SPEC: ASTM B209	B	A											
51707	AL 3105-H25 SHEET SPEC: ASTM B209	B	A											
51702	AL 3105-O SHEET SPEC: ASTM B209	B	A											
50981	AL 354.0-T4 CASTINGS PERMANENT MOLD SPEC: MIL-A-21180D	B	A											
52943	AL 354.0-T4 CASTINGS SAND (WITH CHILLS) SPEC: MIL-A-21180D	B	A											
52942	AL 354.0-T4 CASTINGS SPECIAL MOLD SPEC: MIL-A-21180D	B	A											

MSFC-HDBK-527 REV F 9999942 0004871 7

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	LH2 RTG	LH2 PRESS	LH2 TEMP
50982	AL 354.0-T6 CASTINGS PERMANENT MOLD SPEC: MIL-A-21180D		B	A											
52945	AL 354.0-T6 CASTINGS SAND (WITH CHILLS) SPEC: MIL-A-21180D		B	A											
52944	AL 354.0-T6 CASTINGS SPECIAL MOLD SPEC: MIL-A-21180D		B	A											
50983	AL 354.0-T61 CASTINGS PERMANENT MOLD SPEC: MIL-A-21180D		B	A											
52947	AL 354.0-T61 CASTINGS SAND (WITH CHILLS) SPEC: MIL-A-21180D		B	A											
52946	AL 354.0-T61 CASTINGS SPECIAL MOLD SPEC: MIL-A-21180D		B	A											
50984	AL 354.0-T62 CASTINGS PERMANENT MOLD SPEC: MIL-A-21180D		B	A											
52949	AL 354.0-T62 CASTINGS SAND (WITH CHILLS) SPEC: MIL-A-21180D		B	A											
52948	AL 354.0-T62 CASTINGS SPECIAL MOLD SPEC: MIL-A-21180D		B	A											
10639	AL 355.0 CASTING SPEC: MIL-A-21180		B	A	A		A	A		A		A	A		
51561	AL 355.0-T51 CASTINGS SAND SPEC: AMS 4210F	QQ-A-601	B	A	A		A	A		A		A	A		
51557	AL 355.0-T6 CASTINGS PERMAMENT MOLD SPEC: QQ-A-596		B	A	A		A	A		A		A	A		
51560	AL 355.0-T6 CASTINGS SAND SPEC: AMS 4212E	QQ-A-601	B	A	A		A	A		A		A	A		
51558	AL 355.0-T71 CASTINGS PERMANENT MOLD SPEC: AMS 4280E	QQ-A-596	B	A	A		A	A		A		A	A		
51559	AL 355.0-T71 CASTINGS SAND SPEC: AMS 4214D	QQ-A-601	B	A	A		A	A		A		A	A		
10051	AL 356.0-O CASTINGS SAND SPEC: QQ-A-601		B	A	A	1000	A	A		A		A	A		
51225	AL 356.0-T51 CASTINGS INVESTMENT SPEC: AMS 4261C		B	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004872 9

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10050	AL 356.0-T51 CASTINGS PERMANENT MOLD SPEC: AMS 4286D	QQ-A-596	B	A	A	1000	A	A		A		A	A		
10517	AL 356.0-T6 CASTINGS SPEC: AMS 4260 QQ-A-601	QQ-A-596	B	A	A	1000	A	A		A		A	A		
51227	AL 356.0-T6 CASTINGS CENTRIFUGAL SPEC: AMS 4285A		B	A	A		A	A		A		A	A		
10052	AL 356.0-T6 CASTINGS INVESTMENT SPEC: AMS 4260C		B	A	A	1000	A	A		A		A	A		
51226	AL 356.0-T6 CASTINGS PERMANENT MOLD SPEC: AMS 4284E	QQ-A-596	B	A	A		A	A		A		A	A		
50516	AL 356.0-T6 CASTINGS SAND SPEC: AMS 4217F	QQ-A-601	B	A	A		A	A		A		A	A		
50270	AL 356.0-T7 CASTING MOLD		B	A	A		A	A		A		A	A		
52491	AL 357.0		B	A	A		A	A		A		A	A		
10293	AL 357.0-F CASTINGS PERMANENT MOLD SPEC: MIL-A-21180D		B	A	A	1000	A	A		A		A	A		
50513	AL 357.0-T6 CASTING		B	A	A		A	A		A		A	A		
51228	AL 359.0-T61 CASTINGS SPEC: MIL-A-21180D		B	A											
52493	AL 364-F CASTINGS DIE		B	A											
10636	AL 380 CASTINGS SPEC: QQ-A-591 CP-380		B	A	A		A	A		A		A	A		
51826	AL 4032-T6 FORGING DIE SPEC: ASTM B247	QQ-A-367H	B	B											
51814	AL 4043 ELECTRODES WELDING SPEC: MIL-E-16053	QQ-R-566	B	N											
51813	AL 4043 ROD WELDING SPEC: QQ-R-566		B	N											
51687	AL 4043 WIRE SPRAY GUN SPEC: MIL-W-6712		B	N											
51684	AL 4043-F ROD WELDING SPEC: AMS 4190		B	N											

MSFC-HDBK-527 REV F 9999942 0004873 0

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51685	AL 4043-F WIRE WELDING SPEC: AMS 4190		B	N											
51686	AL 4043-T6 ELECTRODES WELDING SPEC: MIL-E-16053L		B	N											
51688	AL 4043-T651 ELECTRODES WELDING SPEC: MIL-E-16053L		B	N											
51202	AL 4045 METAL BRAZING FILLER SPEC: QQ-B-655		B	N											
51835	AL 4047 ELECTRODES WELDING SPEC: MIL-E-16053	QQ-R-566	B	N											
51832	AL 4047 METAL BRAZING FILLER SPEC: AMS 4185 QQ-B-655	MIL-B-20148	B	N											
51833	AL 4047 ROD WELDING SPEC: QQ-R-566		B	N											
51834	AL 4047-T651 ELECTRODES WELDING SPEC: MIL-E-16053		B	N											
53085	AL 4145 ELECTRODES WELDING SPEC: QQ-R-566														
51823	AL 4145 METAL BRAZING FILLER SPEC: AMS 4184 QQ-B-655	MIL-B-20148	B	N											
51824	AL 4145 ROD WELDING SPEC: QQ-R-566		B	N											
51825	AL 4145-O ELECTRODES WELDING SPEC: MIL-E-16053		B	N											
10641	AL 43 CASTING INGOT SPEC: QQ-A-371		B	A	A		U	U		U		A	A		
10672	AL 4343 METAL BRAZING FILLER SPEC: QQ-B-655		B	N	A		A	A		A		A	A		
51184	AL 4643		B	N											
51659	AL 5005-H112 PLATE SPEC: ASTM B209		B	A											
51648	AL 5005-H12 PLATE SPEC: ASTM B209		B	A											

MSFC-HDBK-527 REV F ■ 9999942 0004874 2 ■

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51647	AL 5005-H12 SHEET SPEC: ASTM B209	B	A											
51650	AL 5005-H14 PLATE SPEC: ASTM B209	B	A											
51649	AL 5005-H14 SHEET SPEC: ASTM B209	B	A											
51651	AL 5005-H16 SHEET SPEC: ASTM B209	B	A											
51652	AL 5005-H18 SHEET SPEC: ASTM B209	B	A											
51661	AL 5005-H19 WIRE SPEC: ASTM B396	B	A											
51654	AL 5005-H32 PLATE SPEC: ASTM B209	B	A											
51665	AL 5005-H32 ROD RIVET AND COLD HEADING SPEC: ASTM B316 QQ-A-430C	B	A											
51653	AL 5005-H32 SHEET SPEC: ASTM B209	B	A											
51664	AL 5005-H32 WIRE RIVET AND COLD HEADING SPEC: ASTM B316 QQ-A-430C	B	A											
51656	AL 5005-H34 PLATE SPEC: ASTM B209	B	A											
51655	AL 5005-H34 SHEET SPEC: ASTM B209	B	A											
51657	AL 5005-H36 SHEET SPEC: ASTM B209	B	A											
51658	AL 5005-H38 SHEET SPEC: ASTM B209	B	A											
51646	AL 5005-O PLATE SPEC: ASTM B209	B	A											
51663	AL 5005-O ROD RIVET AND COLD HEADING SPEC: ASTM B316 QQ-A-430C	B	A											
51660	AL 5005-O ROD ROLLED SPEC: ASTM B531	B	A											

MSFC-HDBK-527 REV F 9999942 0004875 4

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51645	AL 5005-O SHEET SPEC: ASTM B209		B	A											
51666	AL 5005-O TUBE DRAWN SPEC: ASTM B483		B	A											
52599	AL 5005-O TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
51662	AL 5005-O WIRE RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											
51800	AL 5050-H112 PLATE SPEC: ASTM B209		B	A											
51795	AL 5050-H32 SHEET SPEC: ASTM B209		B	A											
51802	AL 5050-H32 TUBE DRAWN SPEC: ASTM B483		B	A											
52595	AL 5050-H32 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
51807	AL 5050-H32 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
51796	AL 5050-H34 SHEET SPEC: ASTM B209		B	A											
51803	AL 5050-H34 TUBE DRAWN SPEC: ASTM B483		B	A											
52596	AL 5050-H34 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
51808	AL 5050-H34 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
52597	AL 5050-H36 SPEC: ASTM B210		B	A											
51797	AL 5050-H36 SHEET SPEC: ASTM B209		B	A											
51804	AL 5050-H36 TUBE DRAWN SPEC: ASTM B483		B	A											
51809	AL 5050-H36 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											

MSFC-HDBK-527 REV F 9999942 0004876 6

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51798	AL 5050-H38 SHEET SPEC: ASTM B209		B	A											
51805	AL 5050-H38 TUBE DRAWN SPEC: ASTM B483		B	A											
52598	AL 5050-H38 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
51810	AL 5050-H38 TUBE WELDED SPEC: ASTM B313		B	A											
51799	AL 5050-O PLATE SPEC: ASTM B209		B	A											
51794	AL 5050-O SHEET SPEC: ASTM B209		B	A											
51801	AL 5050-O TUBE DRAWN SPEC: ASTM B483		B	A											
52594	AL 5050-O TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
51806	AL 5050-O TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
10519	AL 5052 BAR SPEC: QQ-A-225/7		B	A	A		A	A		A		A	A		
50142	AL 5052 CORE HONEYCOMB AEROWEB MANF: AMERICAN CYNAMID SPEC: MIL-C-7438F		B	A	U		U	U		U		U	U		
50128	AL 5052 HONEYCOMB CORE MANF: SIGMUND COHN CORP SPEC: MIL-C-7438C		B	A	U		U	A		A		U	U		
50501	AL 5052 RIVET SPEC: QQ-A-430		B	A	A		A	A		A		A	A		
50604	AL 5052 ROD SPEC: QQ-A-225/7		B	A	A		A	A		A		A	A		
50296	AL 5052 SHEET ANNEALED SPEC: QQ-A-250/8		B	A	A		A	A		A		A	A		
10171	AL 5052 TUBE		B	A	A		A	A		A		A	A		
50605	AL 5052 WIRE SPEC: QQ-A-225/7		B	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004877 8

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52793	AL 5052-F BAR COLD FINISHED SPEC: AMS 4114 QQ-A-225/7	ASTM B211	B	A											
51919	AL 5052-F BAR ROLLED SPEC: AMS 4114 QQ-A-225/7	ASTM B211	B	A											
52792	AL 5052-F ROD COLD FINISHED SPEC: AMS 4114 QQ-A-225/7	ASTM B211	B	A											
51918	AL 5052-F ROD ROLLED SPEC: AMS 4114 QQ-A-225/7	ASTM B211	B	A											
53076	AL 5052-F WIRE COLD FINISHED SPEC: AMS 4114		B	A											
51920	AL 5052-F WIRE ROLLED SPEC: AMS 4114		B	A											
51956	AL 5052-H112 PLATE SPEC: ASTM B209	QQ-A-250/8	B	A											
51947	AL 5052-H112 TUBE ROUND SPEC: ASTM B547		B	A											
51955	AL 5052-H19 FOIL SPEC: MIL-A-81596		B	A											
10033	AL 5052-H191 FOIL SPEC: AMS 4004	MIL-A-81596	B	A	A		A	A		A		A	A		
51953	AL 5052-H22 ROD RIVET SPEC: QQ-A-430C		B	A											
51952	AL 5052-H22 WIRE RIVET SPEC: QQ-A-430C		B	A											
50606	AL 5052-H24 PLATE SPEC: QQ-A-250/8		B	A	A		A	A		A		A	A		
50277	AL 5052-H24 SHEET SPEC: QQ-A-250/8		B	A	A		A	A		A		A	A		
51932	AL 5052-H32 BAR DRAWN SPEC: QQ-A-225/7		B	A											
50607	AL 5052-H32 PLATE SPEC: AMS 4016 MBO170-078	ASTM B209 QQ-A-250/8	B	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F ■ 9999942 0004878 T ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51929	AL 5052-H32 ROD DRAWN SPEC: QQ-A-225/7		B	A											
51951	AL 5052-H32 ROD RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											
10112	AL 5052-H32 SHEET SPEC: AMS 4016 MB0170-078	ASTM B209 QQ-A-250/8	B	A	A		A	A		A		A	A		
51942	AL 5052-H32 TUBE CONDENSER SPEC: ASTM B234		B	A											
51937	AL 5052-H32 TUBE DRAWN SPEC: ASTM B483		B	A											
52796	AL 5052-H32 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/4	B	A											
52806	AL 5052-H32 TUBE ROUND SPEC: ASTM B547		B	A											
52803	AL 5052-H32 TUBE WELDED SPEC: ASTM B313		B	A											
52788	AL 5052-H32 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/7	B	A											
51924	AL 5052-H32 WIRE DRAWN SPEC: QQ-A-225/7		B	A											
51949	AL 5052-H32 WIRE RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											
51914	AL 5052-H32 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/7	B	A											
51933	AL 5052-H34 BAR DRAWN SPEC: QQ-A-225/7		B	A											
50608	AL 5052-H34 PLATE SPEC: AMS 4017 MB0170-078	ASTM B209 QQ-A-250/8	B	A	A		A	A		A		A	A		
51930	AL 5052-H34 ROD DRAWN SPEC: QQ-A-225/7		B	A											
50271	AL 5052-H34 SHEET SPEC: AMS 4017 MB0170-078	ASTM B209 QQ-A-250/8	B	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004879 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51943	AL 5052-H34 TUBE CONDENSER SPEC: ASTM B234		B	A											
51938	AL 5052-H34 TUBE DRAWN SPEC: ASTM B483		B	A											
52797	AL 5052-H34 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/4	B	A											
52807	AL 5052-H34 TUBE ROUND SPEC: ASTM B547		B	A											
52804	AL 5052-H34 TUBE WELDED SPEC: ASTM B313		B	A											
52789	AL 5052-H34 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/7	B	A											
51925	AL 5052-H34 WIRE DRAWN SPEC: QQ-A-225/7		B	A											
51915	AL 5052-H34 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/7	B	A											
51934	AL 5052-H36 BAR DRAWN SPEC: QQ-A-225/7		B	A											
50609	AL 5052-H36 PLATE SPEC: MB0170-078	QQ-A-250/8	B	A	A		A	A		A		A	A		
51921	AL 5052-H36 ROD DRAWN SPEC: QQ-A-225/7		B	A											
10115	AL 5052-H36 SHEET SPEC: ASTM B209 QQ-A-250/8	MB0170-078	B	A	A		A	A		A		A	A		
51939	AL 5052-H36 TUBE DRAWN SPEC: ASTM B483		B	A											
52798	AL 5052-H36 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/4	B	A											
52808	AL 5052-H36 TUBE ROUND SPEC: ASTM B547		B	A											
51945	AL 5052-H36 TUBE WELDED SPEC: ASTM B313		B	A											
52790	AL 5052-H36 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/7	B	A											

MSFC-HDBK-527 REV F 9999942 0004880 8

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDXE RTG	HDXE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51926	AL 5052-H36 WIRE DRAWN SPEC: QQ-A-225/7		B	A											
51916	AL 5052-H36 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/7	B	A											
51935	AL 5052-H38 BAR DRAWN SPEC: QQ-A-225/7		B	A											
50610	AL 5052-H38 PLATE SPEC: MB0170-078	QQ-A-250/8	B	A	A		A	A		A		A	A		
51922	AL 5052-H38 ROD DRAWN SPEC: QQ-A-225/7		B	A											
50274	AL 5052-H38 SHEET SPEC: ASTM B209 QQ-A-250/8	MB0170-078	B	A	A		A	A		A		A	A		
51940	AL 5052-H38 TUBE DRAWN SPEC: ASTM B483		B	A											
52799	AL 5052-H38 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/4	B	A											
51946	AL 5052-H38 TUBE WELDED SPEC: ASTM B313		B	A											
52791	AL 5052-H38 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/7	B	A											
51927	AL 5052-H38 WIRE DRAWN SPEC: QQ-A-225/7		B	A											
51917	AL 5052-H38 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/7	B	A											
52787	AL 5052-O BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/7	B	A											
51931	AL 5052-O BAR DRAWN SPEC: QQ-A-225/7		B	A											
51913	AL 5052-O BAR ROLLED SPEC: ASTM 225/7	ASTM B211	B	A											
51954	AL 5052-O FOIL SPEC: MIL-A-81596		B	A											
50611	AL 5052-O PLATE SPEC: AMS 4015 QQ-A-250/8	ASTM B209	B	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004881 T

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52786	AL 5052-O ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/7	B	A											
51928	AL 5052-O ROD DRAWN SPEC: QQ-A-225/7		B	A											
51950	AL 5052-O ROD RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											
51912	AL 5052-O ROD ROLLED SPEC: ASTM B211	QQ-A-225/7	B	A											
50216	AL 5052-O SHEET SPEC: AMS 4015 QQ-A-250/8	ASTM B209	B	A	A		A	A		A		A			
10500	AL 5052-O TUBE		B	A	A		A	A		A		A	A		
51936	AL 5052-O TUBE DRAWN SPEC: ASTM B483		B	A											
52795	AL 5052-O TUBE DRAWN SEAMLESS SPEC: AMS 4070 WW-T-700/4	ASTM B210	B	A											
52801	AL 5052-O TUBE DRAWN SEAMLESS HYDRAULIC SPEC: AMS 4071		B	A											
52800	AL 5052-O TUBE DRAWN SEAMLESS SPECIAL TOLERANCE SPEC: AMS 4069	WW-T-700/4	B	A											
51941	AL 5052-O TUBE EXTRUDED SPEC: ASTM B221		B	A											
52802	AL 5052-O TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
52805	AL 5052-O TUBE ROUND SPEC: ASTM B547		B	A											
51944	AL 5052-O TUBE WELDED SPEC: ASTM B313		B	A											
52785	AL 5052-O WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/7	B	A											
51923	AL 5052-O WIRE DRAWN SPEC: QQ-A-225/7		B	A											
51948	AL 5052-O WIRE RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											

MSFC-HDBK-527 REV F 9999942 0004882 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51911	AL 5052-O WIRE ROLLED SPEC: ASTM B211	QQ-A-225/7	B	A											
50078	AL 5056 HONEYCOMB CORE SPEC: MIL-C-7438		B	A	U		U	A		A		U	U		
50612	AL 5056 ROD		B	A	A		A	A		A		A	A		
50613	AL 5056 WIRE		B	A	A		A	A		A		A	A		
10377	AL 5056 WIRE SCREEN SPEC: LB0130-018	RR-W-360	B	A	A		A	A		A		A	A		
51214	AL 5056-H111 WIRE ROLLED SPEC: ASTM B211		B	A											
51215	AL 5056-H12 WIRE ROLLED SPEC: ASTM B211		B	A											
51217	AL 5056-H14 WIRE ROLLED SPEC: ASTM B211		B	A											
51219	AL 5056-H18 WIRE ROLLED SPEC: ASTM B211		B	A											
52878	AL 5056-H192 WIRE COLD FINISHED CLAD SPEC: ASTM B211		B	A											
51221	AL 5056-H192 WIRE ROLLED SPEC: ASTM B211		B	A											
51569	AL 5056-H192 WIRE ROLLED CLAD SPEC: ASTM B211		B	A											
51213	AL 5056-H22 ROD RIVET AND COLD HEADING SPEC: QQ-A-430C		B	A											
51212	AL 5056-H22 WIRE RIVET AND COLD HEADING SPEC: QQ-A-430C		B	A											
51211	AL 5056-H32 ROD RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											
51210	AL 5056-H32 WIRE RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											
51216	AL 5056-H32 WIRE ROLLED SPEC: ASTM B211		B	A											
51218	AL 5056-H34 WIRE ROLLED SPEC: ASTM B211		B	A											

MSFC-HDBK-527 REV F 9999942 0004883 3

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50614	AL 5056-H38 PLATE	B	A	A		A	A		A		A	A		
50238	AL 5056-H38 SHEET	B	A	A		A	A		A		A	A		
51220	AL 5056-H38 WIRE ROLLED SPEC: ASTM B211	B	A											
10261	AL 5056-H39 FOIL SPEC: MIL-A-81596	B	A	A	1000	A	X		A		A	A		
52879	AL 5056-H392 WIRE COLD FINISHED CLAD SPEC: ASTM B211	B	A											
51222	AL 5056-H392 WIRE ROLLED SPEC: ASTM B211	B	A											
51570	AL 5056-H392 WIRE ROLLED CLAD SPEC: ASTM B211	B	A											
52880	AL 5056-H393 WIRE COLD FINISHED CLAD SPEC: ASTM B211	B	A											
51571	AL 5056-H393 WIRE ROLLED CLAD SPEC: ASTM B211	B	A											
50275	AL 5056-O BAR ROLLED SPEC: ASTM B211	B	A	A		A	A		A		A	A		
10443	AL 5056-O ROD ROLLED SPEC: ASTM B211	B	A	A		A	A		A		A	A		
50615	AL 5056-O WIRE ROLLED SPEC: AMS 4182 ASTM B211	B	A	A		A	A		A		A	A		
52794	AL 5082-F WIRE COLD FINISHED SPEC: AMS 4114	B	A											
10017	AL 5083-H111 BAR EXTRUDED SPEC: QQ-A-200/4D	B	A	A		A	A		A		A	A		
51251	AL 5083-H111 FORGING DIE SPEC: QQ-A-367H	B	A											
51253	AL 5083-H111 FORGING HAND SPEC: QQ-A-367H	B	A											
50616	AL 5083-H111 ROD EXTRUDED SPEC: QQ-A-200/4D	B	A	A		A	A		A		A	A		
51249	AL 5083-H111 SHAPES EXTRUDED SPEC: QQ-A-200/4D	B	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F ■ 9999942 0004884 5 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51246	AL 5083-H111 TUBE EXTRUDED SPEC: QQ-A-200/4D		B	A	A		A	A		A		A	A		
50617	AL 5083-H111 WIRE EXTRUDED SPEC: QQ-A-200/4D		B	A	A		A	A		A		A	A		
51240	AL 5083-H112 BAR EXTRUDED SPEC: QQ-A-200/4D		B	A											
51252	AL 5083-H112 FORGING DIE SPEC: QQ-A-367H		B	A											
51254	AL 5083-H112 FORGING HAND SPEC: QQ-A-367H		B	A											
51238	AL 5083-H112 PLATE SPEC: QQ-A-250/6G		B	A											
51242	AL 5083-H112 ROD EXTRUDED SPEC: QQ-A-200/4D		B	A											
51250	AL 5083-H112 SHAPES EXTRUDED SPEC: QQ-A-200/4D		B	A											
51247	AL 5083-H112 TUBE EXTRUDED SPEC: QQ-A-200/4D		B	A											
51244	AL 5083-H112 WIRE EXTRUDED SPEC: QQ-A-200/4D		B	A											
50618	AL 5083-H32 PLATE SPEC: MB0170-078	QQ-A-250/6G	B	B	A		A	A		A		A	A		
10016	AL 5083-H32 SHEET SPEC: MB0170-078	QQ-A-250/6G	B	A	A		A	A		A		A	A		
51237	AL 5083-H321 PLATE SPEC: AMS 4059E	QQ-A-250/6G	B	B											
51233	AL 5083-H321 SHEET SPEC: AMS 4059E	QQ-A-250/6G	B	A											
51234	AL 5083-H323 SHEET SPEC: AMS 4057D	QQ-A-250/6G	B	A											
51235	AL 5083-H343 SHEET SPEC: AMS 4058D	QQ-A-250/6G	B	A											
51239	AL 5083-O BAR EXTRUDED SPEC: QQ-A-200/4D		B	U											

MSFC-HDBK-527 REV F ■ 9999942 0004885 7 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51236	AL 5083-O PLATE SPEC: AMS 4056D	QQ-A-250/6G	B	U											
51241	AL 5083-O ROD EXTRUDED SPEC: QQ-A-200/4D		B	U											
51248	AL 5083-O SHAPES EXTRUDED SPEC: QQ-A-200/4D		B	U											
51232	AL 5083-O SHEET SPEC: AMS 4056D	QQ-A-250/6G	B	A											
51245	AL 5083-O TUBE EXTRUDED SPEC: QQ-A-200/4D		B	A											
51243	AL 5083-O WIRE EXTRUDED SPEC: QQ-A-200/4D		B	A											
51012	AL 5086-H111 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/5D	B	A											
51029	AL 5086-H111 PIPE SPEC: ASTM B345		B	A											
51011	AL 5086-H111 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/5D	B	A											
51013	AL 5086-H111 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/5D	B	A											
51014	AL 5086-H111 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/5D	B	A											
52834	AL 5086-H111 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
51010	AL 5086-H111 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/5D	B	A											
51017	AL 5086-H112 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/5D	B	A											
51031	AL 5086-H112 PIPE SPEC: ASTM B345		B	A											
51002	AL 5086-H112 PLATE SPEC: ASTM B209	QQ-A-250/7E	B	A											
51016	AL 5086-H112 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/5D	B	A											

MSFC-HDBK-527 REV F 9999942 0004886 9

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51018	AL 5086-H112 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/5D	B	A											
51001	AL 5086-H112 SHEET SPEC: ASTM B209	QQ-A-250/7E	B	A											
51019	AL 5086-H112 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/5D	B	A											
52835	AL 5086-H112 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
51015	AL 5086-H112 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/5D	B	A											
51004	AL 5086-H116 PLATE SPEC: ASTM B209	QQ-A-250/7E	B	A											
51003	AL 5086-H116 SHEET SPEC: ASTM B209	QQ-A-250/7E	B	A											
50996	AL 5086-H32 PLATE SPEC: ASTM B209	QQ-A-250/7E	B	B											
50995	AL 5086-H32 SHEET SPEC: ASTM B209	QQ-A-250/7E	B	A											
51021	AL 5086-H32 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/5E	B	A											
51025	AL 5086-H32 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
50998	AL 5086-H34 PLATE SPEC: ASTM B209	QQ-A-250/7E	B	B											
50997	AL 5086-H34 SHEET SPEC: ASTM B209	QQ-A-250/7E	B	A											
51022	AL 5086-H34 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/5E	B	A											
51026	AL 5086-H34 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
50999	AL 5086-H36 SHEET SPEC: ASTM B209	QQ-A-250/7E	B	A											
51023	AL 5086-H36 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/5E	B	A											

MSFC-HDBK-527 REV F 9999942 0004887 0

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51027	AL 5086-H36 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
51000	AL 5086-H38 SHEET SPEC: ASTM B209	QQ-A-250/7E	B	A											
51007	AL 5086-O BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/5D	B	B											
51028	AL 5086-O PIPE SPEC: ASTM B345		B	U											
50994	AL 5086-O PLATE SPEC: ASTM B209	QQ-A-250/7E	B	U											
51006	AL 5086-O ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/5D	B	B											
51008	AL 5086-O SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/5D	B	B											
50993	AL 5086-O SHEET SPEC: ASTM B209	QQ-A-250/7E	B	A											
51020	AL 5086-O TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/5E	B	A											
51009	AL 5086-O TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/5D	B	A											
52833	AL 5086-O TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
51024	AL 5086-O TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
51005	AL 5086-O WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/5D	B	A											
53075	AL 5145 ELECTRODES WELDING		B	N											
52842	AL 5154-H112 BAR COLD FINISHED SPEC: ASTM B211		B	A											
52043	AL 5154-H112 BAR EXTRUDED SPEC: ASTM B221		B	A											
52031	AL 5154-H112 BAR ROLLED SPEC: ASTM B211		B	A											
51201	AL 5154-H112 PLATE SPEC: ASTM B209		B	A											

MSFC-HDBK-527 REV F ■ 9999942 0004888 2 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	MDEE RTG	MDEE TEMP	LOH2 RTG	LH2 RTG	LH2 PRESS	LH2 TEMP
52840	AL 5154-H112 ROD COLD FINISHED SPEC: ASTM B211		B	A											
52041	AL 5154-H112 ROD EXTRUDED SPEC: ASTM B221		B	A											
52029	AL 5154-H112 ROD ROLLED SPEC: ASTM B211		B	A											
52045	AL 5154-H112 SHAPES EXTRUDED SPEC: ASTM B221		B	A											
52047	AL 5154-H112 TUBE EXTRUDED SPEC: ASTM B221		B	A											
52844	AL 5154-H112 WIRE COLD FINISHED SPEC: ASTM B211		B	A											
52039	AL 5154-H112 WIRE EXTRUDED SPEC: ASTM B221		B	A											
52033	AL 5154-H112 WIRE ROLLED SPEC: ASTM B211		B	A											
51199	AL 5154-H32 PLATE SPEC: ASTM B209		B	A											
51194	AL 5154-H32 SHEET SPEC: ASTM B209		B	A											
52052	AL 5154-H32 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
52845	AL 5154-H32 WIRE COLD FINISHED SPEC: ASTM B211		B	A											
52034	AL 5154-H32 WIRE ROLLED SPEC: ASTM B211		B	A											
51200	AL 5154-H34 PLATE SPEC: ASTM B209		B	A											
51195	AL 5154-H34 SHEET SPEC: ASTM B209		B	A											
52049	AL 5154-H34 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
52053	AL 5154-H34 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											

MSFC-HDBK-527 REV F 9999942 0004889 4

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52846	AL 5154-H34 WIRE COLD FINISHED SPEC: ASTM B211		B	A											
52035	AL 5154-H34 WIRE ROLLED SPEC: ASTM B211		B	A											
51196	AL 5154-H36 SHEET SPEC: ASTM B209		B	A											
52054	AL 5154-H36 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
52847	AL 5154-H36 WIRE COLD FINISHED SPEC: ASTM B211		B	A											
52036	AL 5154-H36 WIRE ROLLED SPEC: ASTM B211		B	A											
51197	AL 5154-H38 SHEET SPEC: ASTM B209		B	A											
52050	AL 5154-H38 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
52055	AL 5154-H38 TUBE WELDED SPEC: ASTM B313		B	A											
52848	AL 5154-H38 WIRE COLD FINISHED SPEC: ASTM B211		B	A											
52037	AL 5154-H38 WIRE ROLLED SPEC: ASTM B211		B	A											
52841	AL 5154-O BAR COLD FINISHED SPEC: ASTM B211		B	A											
52042	AL 5154-O BAR EXTRUDED SPEC: ASTM B221		B	A											
52030	AL 5154-O BAR ROLLED SPEC: ASTM B211		B	A											
51198	AL 5154-O PLATE SPEC: ASTM B209		B	A											
52839	AL 5154-O ROD COLD FINISHED SPEC: ASTM B211		B	A											
52040	AL 5154-O ROD EXTRUDED SPEC: ASTM B221		B	A											

MSFC-HDBK-527 REV F ■ 9999942 0004890 0 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52028	AL 5154-O ROD ROLLED SPEC: ASTM B211		B	A											
52044	AL 5154-O SHAPES EXTRUDED SPEC: ASTM B221		B	A											
51193	AL 5154-O SHEET SPEC: ASTM B209		B	A											
52048	AL 5154-O TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
52046	AL 5154-O TUBE EXTRUDED SPEC: ASTM B221		B	A											
52051	AL 5154-O TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A											
52843	AL 5154-O WIRE COLD FINISHED SPEC: ASTM B211		B	A											
52038	AL 5154-O WIRE EXTRUDED SPEC: ASTM B221		B	A											
52032	AL 5154-O WIRE ROLLED SPEC: ASTM B211		B	A											
50242	AL 518		B	A	U		U	U		U		U	U		
53077	AL 5183 ELECTRODES WELDING SPEC: QQ-R-566														
51821	AL 5183 ROD WELDING SPEC: QQ-R-566		B	A											
51822	AL 5183-O ELECTRODES WELDING SPEC: MIL-E-16053		B	A											
51137	AL 520.0-T4 CASTINGS SAND SPEC: QQ-A-601F		B	C											
51678	AL 5252-H24 SHEET SPEC: ASTM B209		B	A											
51679	AL 5252-H25 SHEET SPEC: ASTM B209		B	A											
51680	AL 5252-H28 SHEET SPEC: ASTM B209		B	A											
51735	AL 5254-H112 PLATE SPEC: ASTM B209		B	A											

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51737	AL 5254-H112 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
51730	AL 5254-H32 PLATE SPEC: ASTM B209		B	A											
51729	AL 5254-H32 SHEET SPEC: ASTM B209		B	A											
51732	AL 5254-H34 PLATE SPEC: ASTM B209		B	A											
51731	AL 5254-H34 SHEET SPEC: ASTM B209		B	A											
51733	AL 5254-H36 SHEET SPEC: ASTM B209		B	A											
51734	AL 5254-H38 SHEET SPEC: ASTM B209		B	A											
51728	AL 5254-O PLATE SPEC: ASTM B209		B	A											
51727	AL 5254-O SHEET SPEC: ASTM B209		B	A											
51736	AL 5254-O TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
50094	AL 535-O CASTINGS SAND SPEC: QQ-A-601		B	A	U		U	A		A		U	U		
53078	AL 5356 ELECTRODES WELDING SPEC: QQ-R-566														
51836	AL 5356 ROD WELDING SPEC: QQ-R-566		B	A											
51837	AL 5356-O ELECTRODES WELDING SPEC: MIL-E-16053		B	A											
51899	AL 5454-H111 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/6	B	A											
51898	AL 5454-H111 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/6	B	A											
51900	AL 5454-H111 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/6	B	A											

MSFC-HDBK-527 REV F 9999942 0004892 4

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51901	AL 5454-H111 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/6	B	A											
52863	AL 5454-H111 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
51897	AL 5454-H111 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/6	B	A											
51904	AL 5454-H112 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/6	B	A											
51891	AL 5454-H112 PLATE SPEC: ASTM B209	QQ-A-250/10	B	A											
51903	AL 5454-H112 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/6	B	A											
51905	AL 5454-H112 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/6	B	A											
51906	AL 5454-H112 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/6	B	A											
52864	AL 5454-H112 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
51910	AL 5454-H112 TUBE WELDED SPEC: ASTM B547		B	A											
51902	AL 5454-H112 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/6	B	A											
51888	AL 5454-H32 PLATE SPEC: ASTM B209	QQ-A-250/10	B	A											
51887	AL 5454-H32 SHEET SPEC: ASTM B209	QQ-A-250/10	B	A											
52865	AL 5454-H32 TUBE CONDENSER SPEC: ASTM B234		B	A											
51908	AL 5454-H32 TUBE WELDED SPEC: ASTM B547		B	A											
51890	AL 5454-H34 PLATE SPEC: ASTM B209	QQ-A-250/10	B	A											
51889	AL 5454-H34 SHEET SPEC: ASTM B209	QQ-A-250/10	B	A											

MSFC-HDBK-527 REV F 9999942 0004893 6

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52866	AL 5454-H34 TUBE CONDENSER SPEC: ASTM B234		B	A											
51909	AL 5454-H34 TUBE WELDED SPEC: ASTM B547		B	A											
51894	AL 5454-O BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/6	B	A											
51886	AL 5454-O PLATE SPEC: ASTM B209	QQ-A-250/10	B	A											
51893	AL 5454-O ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/6	B	A											
51895	AL 5454-O SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/6	B	A											
51885	AL 5454-O SHEET SPEC: ASTM B209	QQ-A-250/10	B	A											
51896	AL 5454-O TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/6	B	A											
52862	AL 5454-O TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
51907	AL 5454-O TUBE WELDED SPEC: ASTM B547		B	A											
51892	AL 5454-O WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/6	B	A											
10253	AL 5456-H111 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/7	B	A	A		A	A		A		A	A		
50619	AL 5456-H111 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/7	B	A	A		A	A		A		A	A		
52277	AL 5456-H111 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/7	B	A	A		A	A		A		A	A		
52280	AL 5456-H111 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/7	B	A	A		A	A		A		A	A		
52284	AL 5456-H111 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A	A		A	A		A		A	A		
50620	AL 5456-H111 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/7	B	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F ■ 9999942 0004894 8 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDXE RTG	HDXE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10254	AL 5456-H112 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/7	B	A	A		A	A		A		A	A		
50623	AL 5456-H112 PLATE SPEC: ASTM B209 QQ-A-250/9	MBO170-078	B	A	A		A	A		A		A	A		
50621	AL 5456-H112 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/7	B	A											
52278	AL 5456-H112 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/7	B	A											
10203	AL 5456-H112 SHEET SPEC: ASTM B209 QQ-A-250/9	MBO170-078	B	A	A		A	A		A		A	A		
52281	AL 5456-H112 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/7	B	A											
52285	AL 5456-H112 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
50622	AL 5456-H112 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/7	B	A											
52271	AL 5456-H116 PLATE SPEC: ASTM B209	QQ-A-250/9	B	A											
52273	AL 5456-H116 SHEET SPEC: ASTM B209	QQ-A-250/9	B	A											
50624	AL 5456-H321 PLATE SPEC: ASTM B209 QQ-A-250/9	MBO170-078	B	B	A		A	A		A		A	A		
10255	AL 5456-H321 SHEET SPEC: ASTM B209 QQ-A-250/9	MBO170-078	B	A	A		A	A		A		A	A		
50625	AL 5456-H323 PLATE SPEC: MBO170-078	QQ-A-250/9	B	A	A		A	A		A		A	A		
10121	AL 5456-H323 SHEET SPEC: MBO170-078	QQ-A-250/9	B	A	A		A	A		A		A	A		
50626	AL 5456-H343 PLATE SPEC: MBO170-078	QQ-A-250/9	B	A	A		A	A		A		A	A		
10204	AL 5456-H343 SHEET SPEC: MBO170-078	QQ-A-250/9	B	A	A		A	A		A		A	A		

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52274	AL 5456-O BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/7	B	B											
52270	AL 5456-O PLATE SPEC: ASTM B209	QQ-A-250/9	B	B											
52275	AL 5456-O ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/7	B	B											
52276	AL 5456-O SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/7	B	B											
52272	AL 5456-O SHEET SPEC: ASTM B209	QQ-A-250/9	B	A											
52286	AL 5456-O TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
52279	AL 5456-O TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/7	B	A											
52283	AL 5456-O TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
52282	AL 5456-O WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/7	B	A											
51701	AL 5457-O SHEET SPEC: ASTM B209		B	A											
51819	AL 5554 ELECTRODES WELDING SPEC: QQ-R-566			A											
51818	AL 5554 ROD WELDING SPEC: QQ-R-566		B	A											
51820	AL 5554-O ELECTRODES WELDING SPEC: MIL-E-16053		B	A											
50240	AL 5556 SPEC: QQ-A-430		B	A	A		A	A		A		A	A		
51830	AL 5556 ELECTRODES WELDING SPEC: QQ-R-566		B	A											
51829	AL 5556 ROD WELDING SPEC: QQ-R-566		B	A											
51831	AL 5556-O ELECTRODES WELDING SPEC: MIL-E-16053		B	A											

MSFC-HDBK-527 REV F 9999942 0004896 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	MDXE RTG	MDXE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50627	AL 5652 STRIP		B	A											
51724	AL 5652-H112 PLATE SPEC: ASTM B209		B	A											
51726	AL 5652-H112 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
51722	AL 5652-H32 PLATE SPEC: ASTM B209		B	A											
51717	AL 5652-H32 SHEET SPEC: ASTM B209		B	A											
51723	AL 5652-H34 PLATE SPEC: ASTM B209		B	A											
51718	AL 5652-H34 SHEET SPEC: ASTM B209		B	A											
51719	AL 5652-H36 SHEET SPEC: ASTM B209		B	A											
51720	AL 5652-H38 SHEET SPEC: ASTM B209		B	A											
51721	AL 5652-O PLATE SPEC: ASTM B209		B	A	A		A	A		A		A	A		
30188	AL 5652-O SHEET SPEC: ALCOA 5652	ASTM B209	B	A	A		A	A		A		A	A		
51725	AL 5652-O TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
51816	AL 5654 ELECTRODES WELDING SPEC: QQ-R-566		B	N											
51817	AL 5654 WIRE WELDING SPEC: QQ-R-566		B	N											
51815	AL 5654-O ELECTRODES WELDING SPEC: MIL-E-16053		B	N											
51748	AL 5657-H241 SHEET SPEC: ASTM B209		B	A											
51749	AL 5657-H25 SHEET SPEC: ASTM B209		B	A											
51750	AL 5657-H26 SHEET SPEC: ASTM B209		B	A											

MSFC-HDBK-527 REV F 9999942 0004897 3

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51751	AL 5657-H28 SHEET SPEC: ASTM B209	B	A											
50628	AL 5754 PLATE	B	A	A		A	A		A		A	A		
50208	AL 5754 SHEET	B	A	A		A	A		A		A	A		
51183	AL 6003	B	A											
50276	AL 6005-H34 TUBE	B	A	A		A	A		A		A	A		
51742	AL 6005-T1 BAR EXTRUDED SPEC: ASTM B221	B	A											
51740	AL 6005-T1 ROD EXTRUDED SPEC: ASTM B221	B	A											
51744	AL 6005-T1 SHAPES EXTRUDED SPEC: ASTM B221	B	A											
51746	AL 6005-T1 TUBE EXTRUDED SPEC: ASTM B221	B	A											
51738	AL 6005-T1 WIRE EXTRUDED SPEC: ASTM B221	B	A											
51743	AL 6005-T5 BAR EXTRUDED SPEC: ASTM B221	B	A											
51741	AL 6005-T5 ROD EXTRUDED SPEC: ASTM B221	B	A											
51745	AL 6005-T5 SHAPES EXTRUDED SPEC: ASTM B221	B	A											
51747	AL 6005-T5 TUBE EXTRUDED SPEC: ASTM B221	B	A											
51739	AL 6005-T5 WIRE EXTRUDED SPEC: ASTM B221	B	A											
51696	AL 6053-H13 ROD RIVET AND COLD HEADING SPEC: ASTM B316 QQ-A-430C	B	A											
51695	AL 6053-H13 WIRE RIVET AND COLD HEADING SPEC: ASTM B316 QQ-A-430C	B	A											
51698	AL 6053-H23 ROD RIVET AND COLD HEADING SPEC: QQ-A-430C	B	A											
51697	AL 6053-H23 WIRE RIVET AND COLD HEADING SPEC: QQ-A-430C	B	A											

MSFC-HDBK-527 REV F 9999942 0004898 5

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51694	AL 6053-O ROD RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											
51693	AL 6053-O WIRE RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											
50120	AL 6053-T4 RIVET AND COLD HEADING SPEC: MIL-R-5674		B	A	A		A	A		A		U	U		
51692	AL 6053-T61 ROD RIVET AND COLD HEADING SPEC: ASTM B316		B	A											
51691	AL 6053-T61 WIRE RIVET AND COLD HEADING SPEC: ASTM B316		B	A											
50629	AL 6060 PLATE		B	A	A		A	A		A		A	A		
50212	AL 6060 SHEET		B	A	A		A	A		A		A	A		
10218	AL 6061 BAR SPEC: QQ-A-225/8		B	A	A	3000	A	A		A		A	A		
10670	AL 6061 BAR ANNEALED SPEC: AMS 4115 QQ-A-200/8	AMS 4160	B	A	A		A	A		A		A	A		
50631	AL 6061 PLATE ANNEALED SPEC: AMS 4025	QQ-A-250/11	B	A	A		A	A		A		A	A		
10325	AL 6061 SHEET ANNEALED SPEC: AMS 4025	QQ-A-250/11	B	A	A		A	A		A		A	A		
51358	AL 6061-F FORGING DIE SPEC: MIL-A-22771D		B	A											
51360	AL 6061-F FORGING HAND SPEC: MIL-A-22771D		B	A	A		A	X		X		X	X		
51284	AL 6061-F FORGING STOCK SPEC: AMS 4127	AMS 4146	B	A											
51373	AL 6061-F IMPACTS SPEC: MIL-A-12545C		B	A											
51291	AL 6061-F PLATE SPEC: QQ-A-250/11F		B	A											
51362	AL 6061-F RINGS ROLLED SPEC: MIL-A-22771D		B	A											
51288	AL 6061-F SHEET SPEC: QQ-A-250/11F		B	A											

MSFC-HDBK-527 REV F 9999942 0004899 7

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51367	AL 6061-F TUBE DRAWN SEAMLESS SPEC: WW-T-700/6F		B	A											
51377	AL 6061-H112 IMPACTS SPEC: MIL-A-12545C		B	A											
50635	AL 6061-H13 ROD RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A											
50119	AL 6061-H13 WIRE SPEC: QQ-A-430C		B	A	A		A	A		A		U	U		
50636	AL 6061-H13 WIRE RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	A	A		A	A		A		U	U		
51282	AL 6061-H23 ROD RIVET AND COLD HEADING SPEC: QQ-A-430C		B	A											
51281	AL 6061-H23 WIRE RIVET AND COLD HEADING SPEC: QQ-A-430C		B	A											
50269	AL 6061-O BAR ROLLED SPEC: AMS 4115D	QQ-A-225/8E	B	A	A		A	A		A		A	A		
51287	AL 6061-O FOIL SPEC: AMS 4009		B	A											
51372	AL 6061-O IMPACTS SPEC: MIL-A-12545C		B	A											
51270	AL 6061-O PIPE SPEC: ASTM B241	ASTM B345	B	A											
50654	AL 6061-O PLATE SPEC: AMS 4025G QQ-A-250/11F	ASTM B209	B	A	A		A	A		A		A	A		
50632	AL 6061-O ROD DRAWN SPEC: AMS 4115D QQ-A-225/8E	ASTM B211	B	A											
50652	AL 6061-O ROD ROLLED SPEC: AMS 4115D QQ-A-225/8E	ASTM B211	B	A	A		A	A		A		A	A		
51322	AL 6061-O SHAPES SPEC: QQ-A-225/8E		B	A											
51331	AL 6061-O SHAPES EXTRUDED SPEC: AMS 4160D QQ-A-200/8F	ASTM B221	B	A											

MSFC-HDBK-527 REV F 9999942 0004900 T

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50148	AL 6061-O SHEET SPEC: AMS 4025G QQ-A-250/11F	ASTM B209	B	A	A		A	A		A		A	A		
51266	AL 6061-O TUBE SPEC: ASTM B313		B	A											
51261	AL 6061-O TUBE DRAWN SPEC: AMS 4080	ASTM B483	B	A											
51366	AL 6061-O TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/6F	B	A											
51341	AL 6061-O TUBE EXTRUDED SPEC: AMS 4160D QQ-A-200/8F	ASTM B221	B	A											
50653	AL 6061-O WIRE EXTRUDED SPEC: AMS 4160D QQ-A-200/8F	ASTM B221	B	A											
51326	AL 6061-T1 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51323	AL 6061-T1 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51334	AL 6061-T1 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51342	AL 6061-T1 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51351	AL 6061-T1 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
50637	AL 6061-T3 PLATE		B	A	A		A	A		A		A	A		
50241	AL 6061-T3 SHEET SPEC: RB0170-236		B	A	A		A	A		A		A	A		
10019	AL 6061-T4 BAR ROLLED SPEC: AMS 4116D QQ-A-225/8E	ASTM B211	B	A	A		A	A		A		A	A		
51285	AL 6061-T4 FORGING DIE SPEC: AMS 4146		B	A											
51374	AL 6061-T4 IMPACTS SPEC: MIL-A-12545C		B	A											

MSFC-HDBK-527 REV F 9999942 0004901 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51271	AL 6061-T4 PIPE		B	A											
	SPEC: ASTM B241	ASTM B345													
50642	AL 6061-T4 PLATE		B	A	A		A	A		A		A	A		
	SPEC: AMS 4026	ASTM B209													
	MB0170-078	QQ-A-250/11													
51286	AL 6061-T4 RINGS ROLLED		B	A											
	SPEC: AMS 4146														
50640	AL 6061-T4 ROD ROLLED		B	A	A		A	A		A		A	A		
	SPEC: AMS 4116	ASTM B211													
	QQ-A-225/8E														
50634	AL 6061-T4 SHAPES DRAWN		B	A											
	SPEC: QQ-A-225/8														
50641	AL 6061-T4 SHAPES ROLLED		B	A											
	SPEC: AMS 4116	QQ-A-225/8E													
10018	AL 6061-T4 SHEET		B	A	A		A	A		A		A	A		
	SPEC: AMS 4026	ASTM B209													
	MB0170-078	QQ-A-250/11													
10732	AL 6061-T4 TUBE		B	A	A		A	A		A		A	A		
	SPEC: AMS 4161	ASTM B221													
	ASTM B234	ASTM B241													
	ASTM B313	ASTM B345													
	ASTM B483	ASTM B547													
	QQ-A-200/8F	WW-T-700/6													
10021	AL 6061-T4 TUBE DRAWN SEAMLESS		B	A	A		A	A		A		A	A		
	SPEC: ASTM B210	WW-T-700/6F													
50633	AL 6061-T4 WIRE COLD FINISHED		B	A											
	SPEC: AMS 4116	ASTM B211													
	QQ-A-225/8														
51312	AL 6061-T4 WIRE DRAWN		B	A											
	SPEC: QQ-A-225/8E														
51352	AL 6061-T4 WIRE EXTRUDED		B	A											
	SPEC: AMS 4161	ASTM B221													
	QQ-A-200/8F														
51308	AL 6061-T4 WIRE ROLLED		B	A	A		A	A		A		A	A		
	SPEC: AMS 4116	ASTM B211													
	QQ-A-225/8E														
51328	AL 6061-T42 BAR EXTRUDED		B	A											
	SPEC: ASTM B221	QQ-A-200/8F													

MSFC-HDBK-527 REV F 9999942 0004902 3

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51294 .	AL 6061-T42 BAR ROLLED SPEC: ASTM B211	QQ-A-225/8E	B	A											
51274	AL 6061-T42 PIPE SPEC: ASTM B241	ASTM B345	B	A											
51292	AL 6061-T42 PLATE SPEC: ASTM B209	QQ-A-250/11F	B	A											
51321	AL 6061-T42 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51300	AL 6061-T42 ROD ROLLED SPEC: ASTM B211	QQ-A-225/8E	B	A											
51337	AL 6061-T42 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51316	AL 6061-T42 SHAPES ROLLED SPEC: QQ-A-225/8E		B	A											
51289	AL 6061-T42 SHEET SPEC: ASTM B209	QQ-A-250/11F	B	A											
51262	AL 6061-T42 TUBE DRAWN SPEC: ASTM B483		B	A											
51368	AL 6061-T42 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
51345	AL 6061-T42 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/8F	ASTM B241	B	A											
51313	AL 6061-T42 WIRE DRAWN SPEC: QQ-A-225/8E		B	A											
51354	AL 6061-T42 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51309	AL 6061-T42 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/8E	B	A											
51267	AL 6061-T451 TUBE SPEC: ASTM B547		B	A											
51255	AL 6061-T451 WIRE SPEC: ASTM B211		B	A											
51327	AL 6061-T4510 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											

MSFC-HDBK-527 REV F 9999942 0004903 5

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51272	AL 6061-T4510 PIPE SPEC: ASTM B241	ASTM B345	B	A											
51320	AL 6061-T4510 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51335	AL 6061-T4510 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51343	AL 6061-T4510 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/8F	ASTM B241	B	A											
51353	AL 6061-T4510 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
10020	AL 6061-T4511 BAR EXTRUDED SPEC: AMS 4172 QQ-A-200/8	ASTM B221	B	A	A		A	A		A		A	A		
51273	AL 6061-T4511 PIPE SPEC: ASTM B241	ASTM B345	B	A											
50638	AL 6061-T4511 ROD EXTRUDED SPEC: AMS 4172 QQ-A-200/8	ASTM B221	B	A	A		A	A		A		A	A		
51336	AL 6061-T4511 SHAPES EXTRUDED SPEC: AMS 4172 QQ-A-200/8F	ASTM B221	B	A	A		A	A		A		A	A		
51344	AL 6061-T4511 TUBE EXTRUDED SPEC: AMS 4172 QQ-A-200/8F	ASTM B221	B	A	A		A	A		A		A	A		
50639	AL 6061-T4511 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/8	B	A	A		A	A		A		A	A		
51329	AL 6061-T51 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51324	AL 6061-T51 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51338	AL 6061-T51 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51346	AL 6061-T51 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/8F	ASTM B241	B	A											

MSFC-HDBK-527 REV F 9999942 0004904 7

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	NDZH RTG	NDZH TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51355	AL 6061-T51 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51298	AL 6061-T6 BAR COLD FINISHED SPEC: AMS 4117 QQ-A-225/8E	ASTM B211	B	A	A		A	A		A		A	A		
51296	AL 6061-T6 BAR DRAWN SPEC: AMS 4117	QQ-A-225/8E	B	A	A		A	A		A		A	A		
10024	AL 6061-T6 BAR EXTRUDED SPEC: AMS 4150 QQ-A-200/8	ASTM B221	B	A	A		A	A		A		A	A		
10023	AL 6061-T6 BAR ROLLED SPEC: AMS 4117 QQ-A-225/8	ASTM B211	B	A	A		A	A		A		A	A		
51359	AL 6061-T6 FORGING DIE SPEC: AMS 4127 MIL-A-22771D	ASTM B247 QQ-A-367H	B	A	A		A	A		A		A	A		
51361	AL 6061-T6 FORGING HAND SPEC: ASTM B247 QQ-A-367H	MIL-A-22771D	B	A	A		A	A		A		A	A		
51375	AL 6061-T6 IMPACTS SPEC: MIL-A-12545C		B	A	A		A	A		A		A	A		
51369	AL 6061-T6 PIPE SPEC: ASTM B241 ASTM B429	ASTM B345 MIL-P-25995B	B	A	A		A	A		A		A	A		
50645	AL 6061-T6 PLATE SPEC: AMS 4025 MB0170-078	AMS 4027 QQ-A-250/11	B	A	A		A	A		A		A	A		
51363	AL 6061-T6 RINGS ROLLED SPEC: AMS 4127	MIL-A-22771D	B	A	A		A	A		A		A	A		
51305	AL 6061-T6 ROD COLD FINISHED SPEC: AMS 4117 QQ-A-225/8E	ASTM B211	B	A	A		A	A		A		A	A		
51302	AL 6061-T6 ROD DRAWN SPEC: AMS 4117	QQ-A-225/8E	B	A	A		A	A		A		A	A		
50643	AL 6061-T6 ROD EXTRUDED SPEC: AMS 4150 QQ-A-200/8	ASTM B221	B	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004905 9

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51280	AL 6061-T6 ROD RIVET AND COLD HEADING SPEC: ASTM B316		B	A	A		A	A		A		A	A		
50651	AL 6061-T6 ROD ROLLED SPEC: AMS 4117 QQ-A-225/8	ASTM B211	B	A	A		A	A		A		A	A		
50650	AL 6061-T6 SHAPE ROLLED SPEC: AMS 4117	QQ-A-225/8	B	A	A		A	A		A		A	A		
51318	AL 6061-T6 SHAPES DRAWN SPEC: QQ-A-225/8E		B	A	A		A	A		A		A	A		
51332	AL 6061-T6 SHAPES EXTRUDED SPEC: AMS 4150 QQ-A-200/8F	ASTM B221	B	A	A		A	A		A		A	A		
51371	AL 6061-T6 SHAPES EXTRUDED STRUCTURAL SPEC: ASTM B308	QQ-A-200/16A	B	A	A		A	A		A		A	A		
51283	AL 6061-T6 SHAPES STANDARD STRUCTURAL SPEC: AMS 4113		B	A	A		A	A		A		A	A		
10022	AL 6061-T6 SHEET SPEC: AMS 4027 MB0170-078	ASTM B209 QQ-A-250/11	B	A	A		A	A		A		A	A		
50286	AL 6061-T6 STRIP		B	A	A		A	A		A		A	A		
51265	AL 6061-T6 TUBE CONDENSER SPEC: ASTM B234		B	A	A		A	A		A		A	A		
51263	AL 6061-T6 TUBE DRAWN SPEC: AMS 4082	ASTM B483	B	A	A		A	A		A		A	A		
10025	AL 6061-T6 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/6	B	A	A		A	A		A		A	A		
51349	AL 6061-T6 TUBE EXTRUDED SPEC: AMS 4150 QQ-A-200/8F	ASTM B221	B	A	A		A	A		A		A	A		
51268	AL 6061-T6 TUBE WELDED SPEC: ASTM B313	ASTM B547	B	A	A		A	A		A		A	A		
51314	AL 6061-T6 WIRE DRAWN SPEC: AMS 4117	QQ-A-225/8E	B	A	A		A	A		A		A	A		
50644	AL 6061-T6 WIRE EXTRUDED SPEC: AMS 4150 QQ-A-200/8	ASTM B221	B	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F ■ 9999942 0004906 0 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51279	AL 6061-T6 WIRE RIVET AND COLD HEADING SPEC: ASTM B316		B	A	A		A	A		A		A	A		
51310	AL 6061-T6 WIRE ROLLED SPEC: AMS 4117 QQ-A-225/8E	ASTM B211	B	A	A		A	A		A		A	A		
51370	AL 6061-T61 FORGING HAND SPEC: QQ-A-367H		B	A											
51260	AL 6061-T62 BAR EXTRUDED SPEC: ASTM B221		B	A	A		A	A		A		A	A		
51295	AL 6061-T62 BAR ROLLED SPEC: ASTM B211	QQ-A-225/8E	B	A											
51275	AL 6061-T62 PIPE SPEC: ASTM B241	ASTM B345	B	A											
51293	AL 6061-T62 PLATE SPEC: ASTM B209	QQ-A-250/11F	B	A											
51306	AL 6061-T62 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/8E	B	A											
51303	AL 6061-T62 ROD DRAWN SPEC: QQ-A-225/8E		B	A											
51259	AL 6061-T62 ROD EXTRUDED SPEC: ASTM B221		B	A											
51301	AL 6061-T62 ROD ROLLED SPEC: ASTM B211	QQ-A-225/8E	B	A											
51333	AL 6061-T62 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51317	AL 6061-T62 SHAPES ROLLED SPEC: QQ-A-225/8E		B	A											
51290	AL 6061-T62 SHEET SPEC: ASTM B209	QQ-A-250/11F	B	A											
50237	AL 6061-T62 STRIP														
51264	AL 6061-T62 TUBE DRAWN SPEC: ASTM B483		B	A											
51350	AL 6061-T62 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/8F	ASTM B241	B	A											

MSFC-HDBK-527 REV F 9999942 0004907 2

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51311	AL 6061-T62 WIRE SPEC: ASTM B211	QQ-A-225/8E	B	A											
51315	AL 6061-T62 WIRE DRAWN SPEC: QQ-A-225/8E		B	A											
51356	AL 6061-T62 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51299	AL 6061-T651 BAR COLD FINISHED SPEC: AMS 4129 QQ-A-225/8E	ASTM B211	B	A											
51297	AL 6061-T651 BAR DRAWN SPEC: QQ-A-225/8E		B	A											
50646	AL 6061-T651 PLATE SPEC: ASTM B209	QQ-A-250/11	B	A	A		A	A		A		A	A		
51364	AL 6061-T651 RING ROLLED SPEC: MIL-A-22771D		B	A											
51307	AL 6061-T651 ROD COLD FINISHED SPEC: AMS 4129 QQ-A-225/8E	ASTM B211	B	A											
51304	AL 6061-T651 ROD DRAWN SPEC: QQ-A-225/8E		B	A											
51319	AL 6061-T651 SHAPES DRAWN SPEC: QQ-A-225/8E		B	A											
50278	AL 6061-T651 SHEET SPEC: QQ-A-250/11		B	A	A		A	A		A		A	A		
50647	AL 6061-T651 STRIP SPEC: QQ-A-250/11		B	A	A		A	A		A		A	A		
51269	AL 6061-T651 TUBE WELDED SPEC: ASTM B547		B	A											
51257	AL 6061-T651 WIRE SPEC: ASTM B211		B	A											
51330	AL 6061-T6510 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51277	AL 6061-T6510 PIPE SPEC: ASTM B241	ASTM B345	B	A											
51325	AL 6061-T6510 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											

MSFC-HDBK-527 REV F ■ 9999942 0004908 4 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51339	AL 6061-T6510 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51347	AL 6061-T6510 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
51357	AL 6061-T6510 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/8F	B	A											
50299	AL 6061-T6511 BAR EXTRUDED SPEC: AMS 4173 QQ-A-200/8	ASTM B221	B	A	A		A	A		A		A	A		
51278	AL 6061-T6511 PIPE SPEC: ASTM B241	ASTM B345	B	A	A		A	A		A		A	A		
50648	AL 6061-T6511 ROD EXTRUDED SPEC: AMS 4173 QQ-A-200/8	ASTM B221	B	A	A		A	A		A		A	A		
51340	AL 6061-T6511 SHAPES EXTRUDED SPEC: AMS 4173 QQ-A-200/8F	ASTM B221	B	A	A		A	A		A		A	A		
51348	AL 6061-T6511 TUBE EXTRUDED SPEC: AMS 4173 QQ-A-200/8F	ASTM B221	B	A	A		A	A		A		A	A		
50649	AL 6061-T6511 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/8	B	A	A		A	A		A		A	A		
10337	AL 6061-T652 FORGING SPEC: QQ-A-367		B	A	A		A	A		A		A	A		
51365	AL 6061-T652 RINGS ROLLED SPEC: MIL-A-22771D		B	A											
51376	AL 6061-T84 IMPACTS SPEC: MIL-A-12545C		B	A											
51258	AL 6061-T89 WIRE SPEC: ASTM B211		B	A											
51256	AL 6061-T94 WIRE SPEC: ASTM B211		B	A											
52858	AL 6062-T9 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/10	B	A											
52126	AL 6063-O BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A											

MSFC-HDBK-527 REV F 9999942 0004909 6

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52136	AL 6063-O PIPE SPEC: ASTM B345		B	A											
52125	AL 6063-O ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A											
52127	AL 6063-O SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A											
52134	AL 6063-O TUBE DRAWN SPEC: ASTM B483		B	A											
52888	AL 6063-O TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
52128	AL 6063-O TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A											
52885	AL 6063-O TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
52124	AL 6063-O WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A											
52155	AL 6063-T1 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A											
52167	AL 6063-T1 PIPE SPEC: ASTM B345		B	A											
52154	AL 6063-T1 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A											
52156	AL 6063-T1 SHAPES EXTRUDED SPEC: ASTM B221 QQ-A-200/9	ASTM B241	B	A											
52157	AL 6063-T1 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A											
52886	AL 6063-T1 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
52887	AL 6063-T1 TUBE ROUND EXTRUDED SPEC: ASTM B491		B	A											
52153	AL 6063-T1 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A											
52164	AL 6063-T31 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											

MSFC-HDBK-527 REV F 9999942 0004910 2

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52160	AL 6063-T4 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A	A		A	A		A		A	A		
52168	AL 6063-T4 PIPE SPEC: ASTM B345		B	A											
52159	AL 6063-T4 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A	A		A	A		A		A			
52161	AL 6063-T4 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A	A		A	A		A		A	A		
52146	AL 6063-T4 TUBE DRAWN SPEC: ASTM B483		B	A	A		A	A		A		A	A		
52889	AL 6063-T4 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A	A		A	A		A		A	A		
52162	AL 6063-T4 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A	A		A	A		A		A	A		
52893	AL 6063-T4 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
52158	AL 6063-T4 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A	A		A	A		A		A	A		
10394	AL 6063-T42 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A	A		A	A		A		A	A		
52169	AL 6063-T42 PIPE SPEC: ASTM B345		B	A	A		A	A		A		A	A		
50655	AL 6063-T42 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A	A		A	A		A		A	A		
52165	AL 6063-T42 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A	A		A	A		A		A	A		
52151	AL 6063-T42 TUBE DRAWN SPEC: ASTM B483		B	A	A		A	A		A		A	A		
52891	AL 6063-T42 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A	A		A	A		A		A	A		
52166	AL 6063-T42 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A	A		A	A		A		A	A		
52894	AL 6063-T42 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A	A		A	A		A		A	A		

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50656	AL 6063-T42 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A	A		A	A		A		A	A		
52131	AL 6063-T5 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A											
52170	AL 6063-T5 PIPE SPEC: ASTM B345		B	A											
52130	AL 6063-T5 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A											
52132	AL 6063-T5 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A											
52133	AL 6063-T5 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A											
52895	AL 6063-T5 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
52129	AL 6063-T5 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A											
50279	AL 6063-T52 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A	A		A	A		A		A	A		
52171	AL 6063-T52 PIPE SPEC: ASTM B345		B	A	A		A	A		A		A	A		
50657	AL 6063-T52 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A	A		A	A		A		A	A		
52139	AL 6063-T52 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A	A		A	A		A		A	A		
52144	AL 6063-T52 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A	A		A	A		A		A	A		
50658	AL 6063-T52 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/9	B	A	A		A	A		A		A	A		
50970	AL 6063-T6 BAR EXTRUDED SPEC: AMS 4156 QQ-A-200/9	ASTM B221	B	A											
52135	AL 6063-T6 PIPE SPEC: ASTM B241	MIL-P-25995	B	A											
52172	AL 6063-T6 PIPE SPEC: ASTM B345		B	A											

MSFC-HDBK-527 REV F 9999942 0004912 6

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52138	AL 6063-T6 PIPE EXTRUDED STRUCTURAL SPEC: ASTM B429		B	A											
50969	AL 6063-T6 ROD EXTRUDED		B	A											
52141	AL 6063-T6 ROD EXTRUDED SPEC: AMS 4156 QQ-A-200/9	ASTM B221	B	A											
50971	AL 6063-T6 SHAPES EXTRUDED		B	A											
52143	AL 6063-T6 SHAPES EXTRUDED SPEC: AMS 4156 QQ-A-200/9	ASTM B221	B	A											
52147	AL 6063-T6 TUBE DRAWN SPEC: ASTM B483		B	A											
52892	AL 6063-T6 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
50972	AL 6063-T6 TUBE EXTRUDED		B	A											
52145	AL 6063-T6 TUBE EXTRUDED SPEC: AMS 4156 QQ-A-200/9	ASTM B221	B	A											
52896	AL 6063-T6 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
52890	AL 6063-T6 TUBE STRUCTURAL EXTRUDED SPEC: ASTM B429		B	A											
50968	AL 6063-T6 WIRE EXTRUDED		B	A											
52140	AL 6063-T6 WIRE EXTRUDED SPEC: AMS 4156 QQ-A-200/9	ASTM B221	B	A											
52173	AL 6063-T62 PIPE SPEC: ASTM B345		B	A											
52152	AL 6063-T62 TUBE DRAWN SPEC: ASTM B483		B	A											
52897	AL 6063-T62 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
52163	AL 6063-T62 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											

MSFC-HDBK-527 REV F ■ 9999942 0004913 8 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52148	AL 6063-T83 TUBE DRAWN SPEC: ASTM B483		B	A											
52898	AL 6063-T83 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
52149	AL 6063-T831 TUBE DRAWN SPEC: ASTM B483		B	A											
52899	AL 6063-T831 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
52150	AL 6063-T832 TUBE DRAWN SPEC: ASTM B483		B	A											
52900	AL 6063-T832 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
51857	AL 6066-O BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51848	AL 6066-O ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51866	AL 6066-O SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51875	AL 6066-O TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51839	AL 6066-O WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51858	AL 6066-T4 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51849	AL 6066-T4 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51867	AL 6066-T4 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51876	AL 6066-T4 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51840	AL 6066-T4 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51861	AL 6066-T42 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											

MSFC-HDBK-527 REV F 9999942 0004914 T

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51852	AL 6066-T42 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51870	AL 6066-T42 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51879	AL 6066-T42 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51843	AL 6066-T42 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51859	AL 6066-T4510 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51850	AL 6066-T4510 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51868	AL 6066-T4510 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51877	AL 6066-T4510 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51841	AL 6066-T4510 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51860	AL 6066-T4511 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51851	AL 6066-T4511 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51869	AL 6066-T4511 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51878	AL 6066-T4511 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51842	AL 6066-T4511 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51862	AL 6066-T6 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51884	AL 6066-T6 FORGING DIE SPEC: QQ-A-367H		B	A											
51853	AL 6066-T6 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											

MSFC-HDBK-527 REV F 9999942 0004915 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51871	AL 6066-T6 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51880	AL 6066-T6 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51844	AL 6066-T6 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51865	AL 6066-T62 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51856	AL 6066-T62 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51874	AL 6066-T62 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51883	AL 6066-T62 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51847	AL 6066-T62 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51863	AL 6066-T6510 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51854	AL 6066-T6510 ROD EXTRUDED SPEC: ASTM B211	QQ-A-200/10	B	A											
51872	AL 6066-T6510 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51881	AL 6066-T6510 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51845	AL 6066-T6510 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51864	AL 6066-T6511 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51855	AL 6066-T6511 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51873	AL 6066-T6511 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51882	AL 6066-T6511 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											

MSFC-HDBK-527 REV F 9999942 0004916 3

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51846	AL 6066-T6511 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/10	B	A											
51675	AL 6070 IMPACTS SPEC: MIL-A-12545		B	A											
51669	AL 6070-T6 BAR EXTRUDED SPEC: MIL-A-46104		B	A											
51676	AL 6070-T6 PIPE SPEC: ASTM B345		B	A											
51667	AL 6070-T6 ROD EXTRUDED SPEC: MIL-A-46104		B	A											
51671	AL 6070-T6 SHAPES EXTRUDED SPEC: MIL-A-46104		B	A											
51673	AL 6070-T6 TUBE EXTRUDED SPEC: MIL-A-46104		B	A											
51670	AL 6070-T62 BAR EXTRUDED SPEC: MIL-A-46104		B	A											
51677	AL 6070-T62 PIPE SPEC: ASTM B345		B	A											
51668	AL 6070-T62 ROD EXTRUDED SPEC: MIL-A-46104		B	A											
51672	AL 6070-T62 SHAPES EXTRUDED SPEC: MIL-A-46104		B	A											
51674	AL 6070-T62 TUBE EXTRUDED SPEC: MIL-A-46104		B	A											
10736	AL 6101 FORMS EXTRUDED METAL SPEC: ASTM B317		B	A	A		A	A		A		A	A		
50659	AL 6101 FORMS STRUCTURAL METAL		B	A	A		A	A		A		A	A		
51778	AL 6101-H111 CONDUCTOR SPEC: ASTM B317		B	A											
51773	AL 6101-T6 CONDUCTOR SPEC: ASTM B317		B	A											
51774	AL 6101-T61 CONDUCTOR SPEC: ASTM B317		B	A											
51775	AL 6101-T63 CONDUCTOR SPEC: ASTM B317		B	A											

MSFC-HDBK-527 REV F 9999942 0004917 5

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51776	AL 6101-T64 CONDUCTOR SPEC: ASTM B317		B	A											
51777	AL 6101-T65 CONDUCTOR SPEC: ASTM B317		B	A											
51185	AL 6105		B	A											
50989	AL 6151-T6 FORGING DIE SPEC: AMS 4125 QQ-A-367H	MIL-A-22771D	B	A											
50990	AL 6151-T6 RINGS ROLLED SPEC: MIL-A-22771D		B	A											
50991	AL 6151-T652 RINGS ROLLED SPEC: MIL-A-22771D		B	A											
52096	AL 6162-T5 BAR EXTRUDED SPEC: QQ-A-200/17		B	A											
52095	AL 6162-T5 ROD EXTRUDED SPEC: QQ-A-200/17		B	A											
52097	AL 6162-T5 SHAPES EXTRUDED SPEC: QQ-A-200/17		B	A											
52098	AL 6162-T5 TUBE EXTRUDED SPEC: QQ-A-200/17		B	A											
52094	AL 6162-T5 WIRE EXTRUDED SPEC: QQ-A-200/17		B	A											
52101	AL 6162-T5510 BAR EXTRUDED SPEC: QQ-A-200/17		B	A											
52100	AL 6162-T5510 ROD EXTRUDED SPEC: QQ-A-200/17		B	A											
52102	AL 6162-T5510 SHAPES EXTRUDED SPEC: QQ-A-200/17		B	A											
52103	AL 6162-T5510 TUBE EXTRUDED SPEC: QQ-A-200/17		B	A											
52099	AL 6162-T5510 WIRE EXTRUDED SPEC: QQ-A-200/17		B	A											
52106	AL 6162-T5511 BAR EXTRUDED SPEC: QQ-A-200/17		B	A											

MSFC-HDBK-527 REV F 9999942 0004918 7

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52105	AL 6162-T5511 ROD EXTRUDED SPEC: QQ-A-200/17	B	A											
52107	AL 6162-T5511 SHAPES EXTRUDED SPEC: QQ-A-200/17	B	A											
52108	AL 6162-T5511 TUBE EXTRUDED SPEC: QQ-A-200/17	B	A											
52104	AL 6162-T5511 WIRE EXTRUDED SPEC: QQ-A-200/17	B	A											
52111	AL 6162-T6 BAR EXTRUDED SPEC: QQ-A-200/17	B	A											
52110	AL 6162-T6 ROD EXTRUDED SPEC: QQ-A-200/17	B	A											
52112	AL 6162-T6 SHAPES EXTRUDED SPEC: QQ-A-200/17	B	A											
52113	AL 6162-T6 TUBE EXTRUDED SPEC: QQ-A-200/17	B	A											
52109	AL 6162-T6 WIRE EXTRUDED SPEC: QQ-A-200/17	B	A											
52116	AL 6162-T6510 BAR EXTRUDED SPEC: QQ-A-200/17	B	A											
52115	AL 6162-T6510 ROD EXTRUDED SPEC: QQ-A-200/17	B	A											
52117	AL 6162-T6510 SHAPES EXTRUDED SPEC: QQ-A-200/17	B	A											
52118	AL 6162-T6510 TUBE EXTRUDED SPEC: QQ-A-200/17	B	A											
52114	AL 6162-T6510 WIRE EXTRUDED SPEC: QQ-A-200/17	B	A											
52121	AL 6162-T6511 BAR EXTRUDED SPEC: QQ-A-200/17	B	A											
52120	AL 6162-T6511 ROD EXTRUDED SPEC: QQ-A-200/17	B	A											
52122	AL 6162-T6511 SHAPES EXTRUDED SPEC: QQ-A-200/17	B	A											

MSFC-HDBK-527 REV F 9999942 0004919 9

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52123	AL 6162-T6511 TUBE EXTRUDED SPEC: QQ-A-200/17		B	A											
52119	AL 6162-T6511 WIRE EXTRUDED SPEC: QQ-A-200/17		B	A											
51690	AL 6201-T81 CONDUCTOR SPEC: ASTM B399		B	A											
51689	AL 6201-T81 WIRE SPEC: ASTM B398		B	A											
51179	AL 6253		B	A											
10507	AL 6262 BAR SPEC: QQ-A-225/10		B	A	A		A	A		A		A	A		
50660	AL 6262 ROD SPEC: QQ-A-225/10		B	A	A		A	A		A		A	A		
50661	AL 6262 WIRE SPEC: QQ-A-225/10		B	A	A		A	A		A		A	A		
52852	AL 6262-T6 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/10	B	A											
52240	AL 6262-T6 BAR EXTRUDED SPEC: ASTM B221		B	A											
52231	AL 6262-T6 BAR ROLLED SPEC: ASTM B211	QQ-A-225/10	B	A											
52851	AL 6262-T6 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/10	B	A											
52239	AL 6262-T6 ROD EXTRUDED SPEC: ASTM B211 QQ-A-225/10	ASTM B221	B	A											
52230	AL 6262-T6 ROD ROLLED SPEC: ASTM B211	QQ-A-225/10	B	A											
52241	AL 6262-T6 SHAPES EXTRUDED SPEC: ASTM B221		B	A											
52246	AL 6262-T6 TUBE DRAWN SPEC: ASTM B483		B	A											
52861	AL 6262-T6 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											

MSFC-HDBK-527 REV F ■ 9999942 0004920 5 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52242	AL 6262-T6 TUBE EXTRUDED SPEC: ASTM B221		B	A											
52850	AL 6262-T6 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/10	B	A											
52238	AL 6262-T6 WIRE EXTRUDED SPEC: ASTM B221		B	A											
52229	AL 6262-T6 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/10	B	A											
52247	AL 6262-T62 TUBE DRAWN SPEC: ASTM B483		B	A											
52859	AL 6262-T62 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A											
52855	AL 6262-T651 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/10	B	A											
52234	AL 6262-T651 BAR ROLLED SPEC: ASTM B211	QQ-A-225/10	B	A											
52854	AL 6262-T651 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/10	B	A											
52233	AL 6262-T651 ROD ROLLED SPEC: ASTM B211	QQ-A-225/10	B	A											
52853	AL 6262-T651 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/10	B	A											
52232	AL 6262-T651 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/10	B	A											
52245	AL 6262-T6510 BAR EXTRUDED SPEC: ASTM B221		B	A											
52244	AL 6262-T6510 ROD EXTRUDED SPEC: ASTM B221		B	A											
52249	AL 6262-T6510 SHAPES EXTRUDED SPEC: ASTM B221		B	A											
52250	AL 6262-T6510 TUBE EXTRUDED SPEC: ASTM B221		B	A											
52243	AL 6262-T6510 WIRE EXTRUDED SPEC: ASTM B221		B	A											

MSFC-HDBK-527 REV F 9999942 0004921 7

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52253	AL 6262-T6511 BAR EXTRUDED SPEC: ASTM B221		B	A											
52252	AL 6262-T6511 ROD EXTRUDED SPEC: ASTM B221		B	A											
52254	AL 6262-T6511 SHAPES EXTRUDED SPEC: ASTM B221		B	A											
52255	AL 6262-T6511 TUBE EXTRUDED SPEC: ASTM B221		B	A											
52251	AL 6262-T6511 WIRE EXTRUDED SPEC: ASTM B221		B	A											
10752	AL 6262-T9 SPEC: QQ-A-225/10		B	A	A		A	A		A		A	A		
52237	AL 6262-T9 BAR ROLLED SPEC: ASTM B211	QQ-A-225/10	B	A	A		A	A		A		A	A		
52857	AL 6262-T9 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/10	B	A	A		A	A		A		A	A		
52236	AL 6262-T9 ROD ROLLED SPEC: ASTM B211	QQ-A-225/10	B	A	A		A	A		A		A	A		
52248	AL 6262-T9 TUBE DRAWN SPEC: ASTM B483		B	A	A		A	A		A		A	A		
52860	AL 6262-T9 TUBE DRAWN SEAMLESS SPEC: ASTM B210		B	A	A		A	A		A		A	A		
52856	AL 6262-T9 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/10	B	A	A		A	A		A		A	A		
52235	AL 6262-T9 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/10	B	A	A		A	A		A		A	A		
50662	AL 6351 PLATE		B	A	A		A	A		A		A	A		
50214	AL 6351 SHEET		B	A	A		A	A		A		A	A		
51784	AL 6351-T5 PIPE SPEC: ASTM B345		B	A											
51781	AL 6351-T54 BAR EXTRUDED SPEC: ASTM B221		B	A											
51780	AL 6351-T54 ROD EXTRUDED SPEC: ASTM B221		B	A											

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51782	AL 6351-T54 SHAPES EXTRUDED SPEC: ASTM B221	B	A											
51783	AL 6351-T54 TUBE EXTRUDED SPEC: ASTM B221	B	A											
51779	AL 6351-T54 WIRE EXTRUDED SPEC: ASTM B221	B	A											
51785	AL 6351-T6 PIPE SPEC: ASTM B345	B	A											
51577	AL 6463-T1 BAR EXTRUDED SPEC: ASTM B221	B	A											
51576	AL 6463-T1 ROD EXTRUDED SPEC: ASTM B221	B	A											
51578	AL 6463-T1 SHAPES EXTRUDED SPEC: ASTM B221	B	A											
51579	AL 6463-T1 TUBE EXTRUDED SPEC: ASTM B221	B	A											
51575	AL 6463-T1 WIRE EXTRUDED SPEC: ASTM B221	B	A											
51582	AL 6463-T5 BAR EXTRUDED SPEC: ASTM B221	B	A											
51581	AL 6463-T5 ROD EXTRUDED SPEC: ASTM B221	B	A											
51583	AL 6463-T5 SHAPES EXTRUDED SPEC: ASTM B221	B	A											
51580	AL 6463-T5 WIRE EXTRUDED SPEC: ASTM B221	B	A											
51587	AL 6463-T6 BAR EXTRUDED SPEC: ASTM B221	B	A											
51586	AL 6463-T6 ROD EXTRUDED SPEC: ASTM B221	B	A											
51588	AL 6463-T6 SHAPES EXTRUDED SPEC: ASTM B221	B	A											
51589	AL 6463-T6 TUBE EXTRUDED SPEC: ASTM B221	B	A											

MSFC-HDBK-527 REV F 9999942 0004923 0

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51585	AL 6463-T6 WIRE EXTRUDED SPEC: ASTM B221	B	A											
51584	AL 6563-T5 TUBE EXTRUDED SPEC: ASTM B221	B	A											
51186	AL 6951	B	A											
10309	AL 6951 SHEET CLAD W/AL 4045 SPEC: MIL-B-20148 CL6	B	A	A		A	A		A		A	A		
51631	AL 7001-O BAR EXTRUDED SPEC: MIL-A-52242	B	N											
51630	AL 7001-O ROD EXTRUDED SPEC: MIL-A-52242	B	N											
51632	AL 7001-O SHAPES EXTRUDED SPEC: MIL-A-52242	B	N											
51634	AL 7001-T6 BAR EXTRUDED SPEC: MIL-A-52242	B	C											
51633	AL 7001-T6 ROD EXTRUDED SPEC: MIL-A-52242	B	C											
51635	AL 7001-T6 SHAPES EXTRUDED SPEC: MIL-A-52242	B	C											
51637	AL 7001-T62 BAR EXTRUDED SPEC: MIL-A-52242	B	C											
51636	AL 7001-T62 ROD EXTRUDED SPEC: MIL-A-52242	B	C											
51638	AL 7001-T62 SHAPES EXTRUDED SPEC: MIL-A-52242	B	C											
51640	AL 7001-T6510 BAR EXTRUDED SPEC: MIL-A-52242	B	C											
51639	AL 7001-T6510 ROD EXTRUDED SPEC: MIL-A-52242	B	C											
51641	AL 7001-T6510 SHAPES EXTRUDED SPEC: MIL-A-52242	B	C											
51643	AL 7001-T6511 BAR EXTRUDED SPEC: MIL-A-52242	B	C											
51642	AL 7001-T6511 ROD EXTRUDED SPEC: MIL-A-52242	B	C											

MSFC-HDBK-527 REV F
9999942 0004924 2
Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDEE RTG	HDEE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51644	AL 7001-T6511 SHAPES EXTRUDED SPEC: MIL-A-52242		B	C											
50288	AL 7005-F SHEET SPEC: UNE-37-105		B	B	A		A	U		U		U	U		
50290	AL 7005-O BAR EXTRUDED SPEC: UNE-37-105		B	C	A		A	U		U		U	U		
50530	AL 7005-O ROD EXTRUDED		B	C	A		A	U		U		U	U		
50287	AL 7005-O SHEET SPEC: UNE-37-105		B	B	A		A	U		U		U	U		
50531	AL 7005-O WIRE EXTRUDED		B	B	A		A	U		U		U	U		
50291	AL 7005-T53 BAR EXTRUDED SPEC: ASTM B221	UNE-37-105	B	C	A		A	U		U		U	U		
50958	AL 7005-T53 ROD EXTRUDED		B	C	A		A	U		U		U	U		
50987	AL 7005-T53 SHAPES EXTRUDED SPEC: ASTM B221		B	C	A		A	U		U		U	U		
50988	AL 7005-T53 TUBE EXTRUDED SPEC: ASTM B221		B	B	A		A	U		U		U	U		
50525	AL 7005-T53 WIRE EXTRUDED		B	B	A		A	U		U		U	U		
50292	AL 7005-T6 BAR EXTRUDED SPEC: UNE-37-105		B	C	A		A	U		U		U	U		
50526	AL 7005-T6 ROD EXTRUDED		B	C	A		A	U		U		U	U		
50289	AL 7005-T6 SHEET SPEC: UNE-37-105		B	B	A		A	U		U		U	U		
50527	AL 7005-T6 WIRE EXTRUDED		B	B	A		A	U		U		U	U		
50284	AL 7005-T62 SHEET		B	B	A		A	A		A		A	A		
50293	AL 7005-T63 BAR EXTRUDED SPEC: UNE-37-105		B	C	A		A	U		U		U	U		
50528	AL 7005-T63 ROD EXTRUDED		B	C	A		A	U		U		U	U		
50529	AL 7005-T63 WIRE EXTRUDED		B	B	A		A	U		U		U	U		
51187	AL 7008		B	N											
51567	AL 7010-T7451 PLATE SPEC: AMS 4205		B	N											

MSFC-HDBK-527 REV F 9999942 0004925 4

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51568	AL 7010-T7651 PLATE		B	B											
10026	AL 7049-T73 FORGING		B	A	A	1000	A	A		X		A	A		
	SPEC: AMS 4111	QQ-A-367V													
51788	AL 7049-T73 FORGING DIE		B	A	A	1000	A	A		X		A	A		
	SPEC: ASTM B247	MIL-A-22771													
	QQ-A-367														
51786	AL 7049-T73 FORGING HAND		B	A	A	1000	A	A		X		A	A		
	SPEC: ASTM B247	MIL-A-22771													
	QQ-A-367														
51793	AL 7049-T7351 PLATE		B	A											
51789	AL 7049-T73510 EXTRUSIONS		B	A											
	SPEC: AMS 4157														
51790	AL 7049-T73511 EXTRUSIONS		B	A											
	SPEC: AMS 4157														
51787	AL 7049-T7352 FORGING HAND		B	A											
	SPEC: ASTM B247	MIL-A-22771													
	QQ-A-367														
51791	AL 7049-T76510 EXTRUSIONS		B	B											
	SPEC: AMS 4159														
51792	AL 7049-T76511 EXTRUSIONS		B	B											
	SPEC: AMS 4159														
52303	AL 7050-H13 ROD RIVET AND COLD HEADING		B	A											
	SPEC: ASTM B316	QQ-A-430C													
52301	AL 7050-H13 WIRE RIVET AND COLD HEADING		B	A											
	SPEC: ASTM B316	QQ-A-430C													
50964	AL 7050-O FORGING DIE		B	U											
50963	AL 7050-O FORGING HAND		B	U											
52302	AL 7050-O ROD RIVET AND COLD HEADING		B	U											
	SPEC: ASTM B316	QQ-A-430C													
52300	AL 7050-O WIRE RIVET AND COLD HEADING		B	U											
	SPEC: ASTM B316	QQ-A-430C													
50966	AL 7050-T411 FORGING DIE		B	N											
52305	AL 7050-T7 ROD RIVET AND COLD HEADING		B	A											
	SPEC: ASTM B316														

MSFC-HDBK-527 REV F ■ 9999942 0004926 6 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52304	AL 7050-T7 WIRE RIVET AND COLD HEADING SPEC: ASTM B316		B	A											
30029	AL 7050-T7351 SHEET & PLATE		B	A											
52294	AL 7050-T73511 BAR EXTRUDED SPEC: AMS 4341		B	A											
52293	AL 7050-T73511 ROD EXTRUDED SPEC: AMS 4341		B	A											
52292	AL 7050-T73511 WIRE EXTRUDED SPEC: AMS 4341		B	A											
50965	AL 7050-T736 FORGING DIE		B	B											
50524	AL 7050-T73651 & T76 SHEET & PLATE		B	B											
50976	AL 7050-T73652 FORGING DIE		B	B											
52299	AL 7050-T74 FORGING DIE SPEC: AMS 4107 MIL-A-22771D	ASTM B247	B	U											
52288	AL 7050-T7451 PLATE SPEC: AMS 4050		B	U											
52297	AL 7050-T74511 BAR EXTRUDED SPEC: AMS 4342		B	U											
52296	AL 7050-T74511 ROD EXTRUDED SPEC: AMS 4342		B	U											
52295	AL 7050-T74511 WIRE EXTRUDED SPEC: AMS 4342		B	U											
52298	AL 7050-T7452 FORGING HAND SPEC: AMS 4108 MIL-A-22771D	ASTM B247	B	U											
52287	AL 7050-T7651 PLATE SPEC: AMS 4201		B	B											
52291	AL 7050-T76511 BAR EXTRUDED SPEC: AMS 4340		B	B											
52290	AL 7050-T76511 ROD EXTRUDED SPEC: AMS 4340		B	B											
52289	AL 7050-T76511 WIRE EXTRUDED SPEC: AMS 4340		B	B											

MSFC-HDBK-527 REV F 9999942 0004927 8

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51189	AL 7072		B	N											
50181	AL 7075 FORGING		B	N	A		A	A		X		A	A		
10454	AL 7075 FORGING HAND SPEC: MB0170-098		B	N	A		A	A		X		A	A		
51498	AL 7075-H13 ROD RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	B											
51497	AL 7075-H13 WIRE RIVET AND COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	B											
51502	AL 7075-H23 ROD RIVET AND COLD HEADING SPEC: QQ-A-430C		B	B											
51501	AL 7075-H23 WIRE RIVET AND COLD HEADING SPEC: QQ-A-430C		B	B											
51386	AL 7075-O BAR COLD FINISHED SPEC: AMS 4187 QQ-A-225/9	ASTM B211	B	N											
51426	AL 7075-O BAR DRAWN SPEC: AMS 4187	QQ-A-225/9	B	N											
51456	AL 7075-O BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/11	B	N											
51385	AL 7075-O BAR ROLLED SPEC: AMS 4187 QQ-A-225/9	ASTM B211	B	N											
51495	AL 7075-O IMPACTS SPEC: MIL-A-12545A		B	N											
51379	AL 7075-O PLATE SPEC: AMS 4044 QQ-A-250/12	ASTM B209	B	N											
52462	AL 7075-O PLATE 1 1/2% CLAD		B	N											
52464	AL 7075-O PLATE 2 1/2% ONE SIDE CLAD		B	N											
52432	AL 7075-O PLATE CLAD SPEC: AMS 4048 QQ-A-250/13	ASTM B209	B	N											
52474	AL 7075-O PLATE CLAD W/7008		B	N											
52469	AL 7075-O PLATE CLAD W/7011 SPEC: AMS 4196	QQ-A-250/26	B	N											

MSFC-HDBK-527 REV F 9999942 0004928 T

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	MDZE RTG	MDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52451	AL 7075-O PLATE ONE SIDE CLAD SPEC: ASTM B209	QQ-A-250/18	B	N											
52910	AL 7075-O RIVET AND ROD COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	N											
52909	AL 7075-O RIVET AND WIRE COLD HEADING SPEC: ASTM B316	QQ-A-430C	B	N											
52913	AL 7075-O ROD COLD FINISHED SPEC: AMS 4187 QQ-A-225/9	ASTM B211	B	N											
52915	AL 7075-O ROD DRAWN SPEC: AMS 4187	QQ-A-225/9	B	N											
52919	AL 7075-O ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/11	B	N											
52912	AL 7075-O ROD ROLLED SPEC: AMS 4187 QQ-A-225/9	ASTM B211	B	N											
51457	AL 7075-O SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/11	B	N											
51378	AL 7075-O SHEET SPEC: AMS 4044 QQ-A-250/12	ASTM B209	B	N											
52461	AL 7075-O SHEET 2 1/2% CLAD		B	N											
52463	AL 7075-O SHEET 2 1/2% ONE SIDE CLAD		B	N											
52430	AL 7075-O SHEET CLAD SPEC: AMS 4048 QQ-A-250/13	ASTM B209	B	N											
52473	AL 7075-O SHEET CLAD W/7008		B	N											
52465	AL 7075-O SHEET CLAD W/7011 SPEC: AMS 4196	QQ-A-250/26	B	N											
52448	AL 7075-O SHEET ONE SIDE CLAD SPEC: ASTM B209	QQ-A-250/18	B	N											
51477	AL 7075-O TUBE DRAWN SPEC: ASTM B210	WW-T-700/7	B	N											
52932	AL 7075-O TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/7	B	N											

MSFC-HDBK-527 REV F 9999942 0004929 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51458	AL 7075-O TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/11	ASTM B241	B	N											
52920	AL 7075-O TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	N											
52911	AL 7075-O WIRE COLD FINISHED SPEC: AMS 4187 QQ-A-225/9	ASTM B211	B	N											
52914	AL 7075-O WIRE DRAWN SPEC: AMS 4187	QQ-A-225/9	B	N											
52918	AL 7075-O WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/11	B	N											
50674	AL 7075-O WIRE ROLLED SPEC: AMS 4187 QQ-A-225/9	ASTM B211	B	N											
50663	AL 7075-T43 PLATE SPEC: QQ-A-250/12		B	C	A		A	U		U		U	U		
50664	AL 7075-T43 ROD EXTRUDED SPEC: QQ-A-200/11		B	C											
50230	AL 7075-T43 SHEET SPEC: RBO170-236		B	B	A		A	U		U		U	U		
51392	AL 7075-T6 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/9	B	C											
51427	AL 7075-T6 BAR DRAWN SPEC: QQ-A-225/9		B	C											
51461	AL 7075-T6 BAR EXTRUDED SPEC: AMS 4154 QQ-A-200/11	ASTM B221	B	C											
51391	AL 7075-T6 BAR ROLLED SPEC: AMS 4122 QQ-A-225/9	ASTM B211	B	C											
50101	AL 7075-T6 FORGING SPEC: AMS 4126 MIL-A-22771D	ASTM B247 QQ-A-367	B	C	A		A	A		X		A	A		
52928	AL 7075-T6 FORGING DIE SPEC: AMS 4126 MIL-A-22771D	ASTM B247 QQ-A-367H	B	C	A		A	A		X		A	A		

MSFC-HDBK-527 REV F ■ 9999942 0004930 8 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZK RTG	HDZK TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52930	AL 7075-T6 FORGING HAND SPEC: ASTM B247 QQ-A-367H	MIL-A-22771D	B	C	A		A	A		X		A	A		
51496	AL 7075-T6 IMPACTS SPEC: AMS 4170	MIL-A-12545A	B	C											
52436	AL 7075-T6 PLATE CLAD SPEC: AMS 4049		B	C	A	1000	A	A		X		A	A		
52454	AL 7075-T6 PLATE ONE SIDE CLAD SPEC: AMS 4046		B	C											
51491	AL 7075-T6 RINGS ROLLED SPEC: MIL-A-22771D		B	C											
51390	AL 7075-T6 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/9	B	C											
51421	AL 7075-T6 ROD DRAWN SPEC: QQ-A-225/9		B	C											
51460	AL 7075-T6 ROD EXTRUDED SPEC: AMS 4154 QQ-A-200/11	ASTM B221	B	C											
51389	AL 7075-T6 ROD ROLLED SPEC: AMS 4122 QQ-A-225/9	ASTM B211	B	C											
51462	AL 7075-T6 SHAPES EXTRUDED SPEC: AMS 4154 QQ-A-200/11	ASTM B221	B	C											
10028	AL 7075-T6 SHEET SPEC: AMS 4045 QQ-A-250/12	ASTM B209	B	B	A	1000	A	A		X		A	A		
52520	AL 7075-T6 SHEET 2 1/2% CLAD		B	B											
10457	AL 7075-T6 SHEET CLAD SPEC: AMS 4049 QQ-A-250/13	ASTM B209	B	B	A	1000	A	A		X		A	A		
52532	AL 7075-T6 SHEET CLAD W/7008		B	B											
52466	AL 7075-T6 SHEET CLAD W/7011 SPEC: AMS 4197	QQ-A-250/26	B	B											
52528	AL 7075-T6 SHEET ONE SIDE 2 1/2% CLAD		B	B											

MSFC-HDBK-527 REV F 9999942 0004931 T

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52449	AL 7075-T6 SHEET ONE SIDE CLAD SPEC: AMS 4046 QQ-A-250/18	ASTM B209	B	B											
51478	AL 7075-T6 TUBE DRAWN SPEC: ASTM B210	WW-T-700/7	B	B											
52933	AL 7075-T6 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/7	B	B											
51463	AL 7075-T6 TUBE EXTRUDED SPEC: AMS 4154 ASTM B241	ASTM B221 QQ-A-200/11	B	B											
52921	AL 7075-T6 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
51388	AL 7075-T6 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/9	B	B											
51416	AL 7075-T6 WIRE DRAWN SPEC: QQ-A-225/9		B	B											
51459	AL 7075-T6 WIRE EXTRUDED SPEC: AMS 4154 QQ-A-200/11	ASTM B221	B	B											
51387	AL 7075-T6 WIRE ROLLED SPEC: AMS 4122 QQ-A-225/9	ASTM B211	B	B											
51398	AL 7075-T62 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/9	B	C											
51428	AL 7075-T62 BAR DRAWN SPEC: QQ-A-225/9		B	C											
30122	AL 7075-T62 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/11	B	B	A		A	A		X		A	A		
51397	AL 7075-T62 BAR ROLLED SPEC: ASTM B211	QQ-A-225/9	B	C											
51381	AL 7075-T62 PLATE SPEC: ASTM B209	QQ-A-250/12	B	C											
52521	AL 7075-T62 PLATE 2 1/2% CLAD		B	C											
52433	AL 7075-T62 PLATE CLAD SPEC: ASTM B209	QQ-A-250/13	B	C											

MSFC-HDBK-527 REV F 9999942 0004932 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52470	AL 7075-T62 PLATE CLAD W/7011 SPEC: QQ-A-250/26		B	C											
52529	AL 7075-T62 PLATE ONE SIDE 2 1/2% CLAD		B	C											
52452	AL 7075-T62 PLATE ONE SIDE CLAD SPEC: QQ-A-250/18		B	C											
52533	AL 7075-T62 PLATE W/7008		B	C											
51396	AL 7075-T62 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/9		C											
51422	AL 7075-T62 ROD DRAWN SPEC: QQ-A-225/9		B	C											
51464	AL 7075-T62 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/11	B	C	A		A	A		X		A	A		
51395	AL 7075-T62 ROD ROLLED SPEC: ASTM B211	QQ-A-225/9	B	C											
51465	AL 7075-T62 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/11	B	C	A		A	A		X		A	A		
51380	AL 7075-T62 SHEET SPEC: ASTM B209	QQ-A-250/12	B	B											
52522	AL 7075-T62 SHEET 2 1/2% CLAD		B												
52431	AL 7075-T62 SHEET CLAD SPEC: ASTM B209	QQ-A-250/13	B	B											
52534	AL 7075-T62 SHEET CLAD W/7008		B	B											
52467	AL 7075-T62 SHEET CLAD W/7011 SPEC: QQ-A-250/26		B	B											
52530	AL 7075-T62 SHEET ONE SIDE 2 1/2% CLAD		B	B											
52450	AL 7075-T62 SHEET ONE SIDE CLAD SPEC: ASTM B209	QQ-A-250/18	B	B											
51479	AL 7075-T62 TUBE DRAWN SPEC: ASTM B210	WW-T-700/7	B	B											
52934	AL 7075-T62 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/7	B	B											
51466	AL 7075-T62 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/11	ASTM B241	B	B											

MSFC-HDBK-527 REV F 9999942 0004933 3

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52922	AL 7075-T62 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
51394	AL 7075-T62 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/9	B	B											
51417	AL 7075-T62 WIRE DRAWN SPEC: QQ-A-225/9		B	B											
50665	AL 7075-T62 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/11	B	B	A		A	A		X		A	A		
51393	AL 7075-T62 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/9	B	B											
51404	AL 7075-T651 BAR COLD FINISHED SPEC: AMS 4123 QQ-A-225/9	ASTM B211	B	C											
51429	AL 7075-T651 BAR DRAWN SPEC: QQ-A-225/9		B	C											
51403	AL 7075-T651 BAR ROLLED SPEC: AMS 4123 QQ-A-225/9	ASTM B211	B	C											
51382	AL 7075-T651 PLATE SPEC: AMS 4045 QQ-A-250/12	ASTM B209	B	C											
52523	AL 7075-T651 PLATE 2 1/2% CLAD		B	C											
52434	AL 7075-T651 PLATE CLAD SPEC: AMS 4039 QQ-A-250/13	ASTM B209	B	C											
52435	AL 7075-T651 PLATE CLAD SPEC: AMS 4039	ASTM B209	B	C											
52535	AL 7075-T651 PLATE CLAD W/7008		B	C											
52471	AL 7075-T651 PLATE CLAD W/7011 SPEC: AMS 4197	QQ-A-250/26	B	C											
52531	AL 7075-T651 PLATE ONE SIDE 2 1/2% CLAD		B	C											
52453	AL 7075-T651 PLATE ONE SIDE CLAD SPEC: ASTM B209	QQ-A-250/18	B	C											
51402	AL 7075-T651 ROD COLD FINISHED SPEC: AMS 4123 QQ-A-225/9	ASTM B211	B	C											

MSFC-HDBK-527 REV F 9999942 0004934 5

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDIE RTG	HDIE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51423	AL 7075-T651 ROD DRAWN SPEC: QQ-A-225/9		B	C											
51401	AL 7075-T651 ROD ROLLED SPEC: AMS 4123 QQ-A-225/9	ASTM B211	B	C											
51400	AL 7075-T651 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/9	B	B											
51418	AL 7075-T651 WIRE DRAWN SPEC: QQ-A-225/9		B	B											
51399	AL 7075-T651 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/9	B	B											
51469	AL 7075-T6510 BAR EXTRUDED SPEC: AMS 4168 QQ-A-200/11	ASTM B221	B	C											
51468	AL 7075-T6510 ROD EXTRUDED SPEC: AMS 4168 QQ-A-200/11	ASTM B221	B	C											
51470	AL 7075-T6510 SHAPES EXTRUDED SPEC: AMS 4168 QQ-A-200/11	ASTM B221	B	C											
51471	AL 7075-T6510 TUBE EXTRUDED SPEC: AMS 4168 ASTM B241	ASTM B221 QQ-A-200/11	B	B											
52923	AL 7075-T6510 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
51467	AL 7075-T6510 WIRE EXTRUDED SPEC: AMS 4168 QQ-A-200/11	ASTM B221	B	B											
51474	AL 7075-T6511 BAR EXTRUDED SPEC: AMS 4169 QQ-A-200/11	ASTM B221	B	C											
51473	AL 7075-T6511 ROD EXTRUDED SPEC: AMS 4169 QQ-A-200/11	ASTM B221	B	C											
51475	AL 7075-T6511 SHAPES EXTRUDED SPEC: AMS 4169 QQ-A-200/11	ASTM B221	B	C											

MSFC-HDBK-527 REV F 9999942 0004935 7

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51476	AL 7075-T6511 TUBE EXTRUDED SPEC: AMS 4169 ASTM B241	ASTM B221 QQ-A-200/11	B	B											
52924	AL 7075-T6511 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
51472	AL 7075-T6511 WIRE EXTRUDED SPEC: AMS 4169 QQ-A-200/11	ASTM B221	B	B											
51486	AL 7075-T652 FORGING HAND SPEC: ASTM B247 QQ-A-367H	MIL-A-22771D	B	C											
51492	AL 7075-T652 RINGS ROLLED SPEC: MIL-A-22771D		B	C											
51410	AL 7075-T73 BAR COLD FINISHED SPEC: ASTM B211	QQ-A-225/9	B	A											
51430	AL 7075-T73 BAR DRAWN SPEC: QQ-A-225/9		B	A											
51433	AL 7075-T73 BAR EXTRUDED SPEC: AMS 4166 QQ-A-200/11	ASTM B221	B	A	A		A	A		X		A	A		
51409	AL 7075-T73 BAR ROLLED SPEC: ASTM B211	QQ-A-225/9	B	A											
51485	AL 7075-T73 FORGING DIE SPEC: AMS 4141 MIL-A-22771D	ASTM B247 QQ-A-367H	B	A											
51487	AL 7075-T73 FORGING HAND SPEC: ASTM B247 QQ-A-367H	MIL-A-22771D	B	A											
51493	AL 7075-T73 FORGING STOCK SPEC: AMS 4141		B	A											
51503	AL 7075-T73 IMPACTS SPEC: MIL-A-12545A		B	A											
51408	AL 7075-T73 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/9	B	A											
51424	AL 7075-T73 ROD DRAWN SPEC: QQ-A-225/9		B	A											

MSFC-HDBK-527 REV F 9999942 0004936 9

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51432	AL 7075-T73 ROD EXTRUDED SPEC: AMS 4166 QQ-A-200/11	ASTM B221	B	A	A		A	A		X		A	A		
51500	AL 7075-T73 ROD RIVET AND COLD HEADING SPEC: ASTM B316		B	A											
51407	AL 7075-T73 ROD ROLLED SPEC: ASTM B211	QQ-A-225/9	B	A											
51434	AL 7075-T73 SHAPES EXTRUDED SPEC: AMS 4166 QQ-A-200/11	ASTM B221	B	A	A		A	A		X		A	A		
50239	AL 7075-T73 SHEET SPEC: ASTM B209	QQ-A-250/12	B	A											
52524	AL 7075-T73 SHEET 2 1/2% CLAD		B	A											
51480	AL 7075-T73 TUBE DRAWN SPEC: ASTM B210	WW-T-700/7	B	A											
52935	AL 7075-T73 TUBE DRAWN SEAMLESS SPEC: ASTM B210	WW-T-700/7	B	A											
50509	AL 7075-T73 TUBE EXTRUDED SPEC: AMS 4166 QQ-A-200/11	ASTM B221	B	A	A		A	A		X		A	A		
52925	AL 7075-T73 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
51406	AL 7075-T73 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/9	B	A											
51419	AL 7075-T73 WIRE DRAWN SPEC: QQ-A-225/9		B	A											
51431	AL 7075-T73 WIRE EXTRUDED SPEC: AMS 4166 QQ-A-200/11	ASTM B221	B	A	A		A	A		X		A	A		
51499	AL 7075-T73 WIRE RIVET AND COLD HEADING SPEC: ASTM B316		B	A											
51405	AL 7075-T73 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/9	B	A											
51415	AL 7075-T7351 BAR COLD FINISHED SPEC: AMS 4124 QQ-A-225/9	ASTM B211	B	A											

MSFC-HDBK-527 REV F 9999942 0004937 0

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52916	AL 7075-T7351 BAR DRAWN SPEC: QQ-A-225/9		B	A											
10047	AL 7075-T7351 BAR ROLLED SPEC: AMS 4124 QQ-A-225/9	ASTM B211	B	A	A	1000	A	A		X		A	A		
50669	AL 7075-T7351 PLATE SPEC: AMS 4078 MB0170-078	ASTM B209 QQ-A-250/12	B	A											
52525	AL 7075-T7351 PLATE 2 1/2% CLAD		B	A											
51414	AL 7075-T7351 ROD COLD FINISHED SPEC: ASTM B211	QQ-A-225/9	B	A											
51425	AL 7075-T7351 ROD DRAWN SPEC: QQ-A-225/9		B	A											
51413	AL 7075-T7351 ROD ROLLED SPEC: ASTM B211	QQ-A-225/9	B	A	A	1000	A	A		X		A	A		
51412	AL 7075-T7351 WIRE COLD FINISHED SPEC: ASTM B211	QQ-A-225/9	B	A											
51420	AL 7075-T7351 WIRE DRAWN SPEC: QQ-A-225/9		B	A											
51411	AL 7075-T7351 WIRE ROLLED SPEC: ASTM B211	QQ-A-225/9	B	A	A	1000	A	A		X		A	A		
51437	AL 7075-T73510 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/11	B	A											
51436	AL 7075-T73510 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/11	B	A											
51438	AL 7075-T73510 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/11	B	A											
51439	AL 7075-T73510 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/11	ASTM B241	B	A											
52926	AL 7075-T73510 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A											
51435	AL 7075-T73510 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/11	B	A											
10421	AL 7075-T73511 BAR EXTRUDED SPEC: AMS 4167 QQ-A-200/11	ASTM B221	B	A	A	1000	A	A		X		A	A		

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDIE RTG	HDIE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50666	AL 7075-T73511 ROD EXTRUDED SPEC: AMS 4167 QQ-A-200/11	ASTM B221	B	A	A	1000	A	A		X		A	A		
51440	AL 7075-T73511 SHAPES EXTRUDED SPEC: AMS 4167 QQ-A-200/11	ASTM B221	B	A	A	1000	A	A		X		A	A		
52917	AL 7075-T73511 TUBE EXTRUDED SPEC: ASTM B221 QQ-A-200/11	ASTM B241	B	A	A	1000	A	A		X		A	A		
52927	AL 7075-T73511 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	A	A	1000	A	A		X		A	A		
50667	AL 7075-T73511 WIRE EXTRUDED SPEC: AMS 4167 QQ-A-200/11	ASTM B221	B	A	A	1000	A	A		X		A	A		
10048	AL 7075-T7352 FORGING SPEC: AMS 4147 MB0170-091 QQ-A-367	ASTM B247 MIL-A-22771	B	A	A	1000	A	A		X		A	A		
52929	AL 7075-T7352 FORGING DIE SPEC: AMS 4147 QQ-A-22771D	ASTM B247 QQ-A-367H	B	A	A	1000	A	A		X		A	A		
52931	AL 7075-T7352 FORGING HAND SPEC: ASTM B247 QQ-A-367H	MIL-A-22771D	B	A	A	1000	A	A		X		A	A		
51494	AL 7075-T736 FORGING SPEC: AMS 4131		B	B											
50668	AL 7075-T73XX ROD ROLLED DRAWN SPEC: QQ-A-225/9		B	A											
10043	AL 7075-T73XX SHEET SPEC: MB0170-078	QQ-A-250/12	B	A	A	1000	A	A		X		A	A		
51488	AL 7075-T74 FORGING DIE SPEC: MIL-A-22771D		B	U											
51489	AL 7075-T74 FORGING HAND SPEC: MIL-A-22771D		B	U											
51490	AL 7075-T7452 FORGING HAND SPEC: MIL-A-22771D		B	U											
51443	AL 7075-T76 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/15	B	B											

MSFC-HDBK-527 REV F 9999942 0004939 4

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51442	AL 7075-T76 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/15	B	B											
51444	AL 7075-T76 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/15	B	B											
53026	AL 7075-T76 SHEET SPEC: ASTM B209	QQ-A-250/24	B	A											
52526	AL 7075-T76 SHEET 2 1/2% CLAD		B	A											
50091	AL 7075-T76 SHEET CLAD SPEC: ASTM B209	QQ-A-250/25	B	A	A		A	A		X		A	A		
52536	AL 7075-T76 SHEET CLAD W/7008		B	A											
52468	AL 7075-T76 SHEET CLAD W/7011 SPEC: QQ-A-250/26		B	A											
51445	AL 7075-T76 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/15	B	B											
51441	AL 7075-T76 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/15	B	B											
50672	AL 7075-T762 PLATE CLAD SPEC: QQ-A-250/13		B	B			A	A		X		A	A		
50089	AL 7075-T762 SHEET CLAD SPEC: QQ-A-250/13		B	A	A		A	A		X		A	A		
51384	AL 7075-T7651 PLATE SPEC: ASTM B209	QQ-A-250/24	B	B											
52527	AL 7075-T7651 PLATE 2 1/2% CLAD		B	B											
50673	AL 7075-T7651 PLATE CLAD SPEC: ASTM B209	QQ-A-250/25	B	B	A	1000	A	A		X		A	A		
52537	AL 7075-T7651 PLATE CLAD W/7008		B	B											
52472	AL 7075-T7651 PLATE CLAD W/7011 SPEC: QQ-A-250/26		B	B											
50090	AL 7075-T7651 SHEET CLAD SPEC: QQ-A-250/25		B	A	A		A	A		X		A	A		
51448	AL 7075-T76510 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/15	B	B											
51449	AL 7075-T76510 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/15	B	B											

MSFC-HDBK-527 REV F 9999942 0004940 0

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51450	AL 7075-T76510 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/15	B	A											
51446	AL 7075-T76510 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/15	B	A											
51453	AL 7075-T76511 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/15	B	B											
51452	AL 7075-T76511 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/15	B	B											
51454	AL 7075-T76511 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/15	B	B											
51455	AL 7075-T76511 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/15	B	A											
51451	AL 7075-T76511 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/15	B	A											
50671	AL 7075-T76X PLATE CLOSE TOLERANCE SPEC: MB0170-078	QQ-A-250/24	B	B	A	1000	A	A		X		A	A		
10044	AL 7075-T76X SHEET CLOSE TOLERANCE SPEC: MB0170-078	QQ-A-250/24	B	A	A	1000	A	A		X		A	A		
10041	AL 7075-T76XXX EXTR EXFR RES SPEC: MB0170-090	QQ-A-200/15	B	B	A	1000	A	A		X		A	A		
51180	AL 7108		B	N											
51138	AL 712.0-T5 CASTINGS SAND SPEC: QQ-A-601F		B	A											
51229	AL 7149-T73 FORGING DIE SPEC: AMS 4320		B	A											
51230	AL 7149-T73510 EXTRUSIONS SPEC: AMS 4343		B	A											
51231	AL 7149-T73511 EXTRUSIONS SPEC: AMS 4343														
50294	AL 7175-O FORGING HAND SPEC: MIL-A-22771C		B	N	A			U		U		U	U		
51542	AL 7175-T66 FORGING DIE SPEC: AMS 4148		B	C											
51548	AL 7175-T73511 EXTRUSIONS SPEC: AMS 4344		B	A											

MSFC-HDBK-527 REV F 9999942 0004941 2

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50282	AL 7175-T736 FORGING HAND		B	B	A		A	A		A		A	A		
50283	AL 7175-T73652 FORGING HAND SPEC: AMS 4179		B	B	A		A	A		A		A	A		
51543	AL 7175-T74 FORGING DIE SPEC: AMS 4149	MIL-A-22771D	B	N											
51544	AL 7175-T74 FORGING HAND SPEC: AMS 4149	MIL-A-22771D	B	N											
51546	AL 7175-T7452 FORGING DIE SPEC: MIL-A-22771D		B	N											
51545	AL 7175-T7452 FORGING HAND SPEC: AMS 4179	MIL-A-22771D	B	N											
51547	AL 7175-T7454 FORGING DIE SPEC: MIL-A-22771D		B	N											
52227	AL 7178-H13 ROD RIVET AND COLD HEADING SPEC: ASTM B316		B	B											
52224	AL 7178-H13 WIRE RIVET AND COLD HEADING SPEC: ASTM B316		B	B											
52185	AL 7178-O BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	N											
52175	AL 7178-O PLATE SPEC: ASTM B209	QQ-A-250/14D	B	N											
52476	AL 7178-O PLATE CLAD SPEC: AMS 4051 QQ-A-250/15	ASTM B209	B	N											
52184	AL 7178-O ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	N											
52226	AL 7178-O ROD RIVET AND COLD HEADING SPEC: ASTM B316		B	N											
52186	AL 7178-O SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	N											
52174	AL 7178-O SHEET SPEC: ASTM B209	QQ-A-250/14D	B	N											
52475	AL 7178-O SHEET CLAD SPEC: AMS 4051 QQ-A-250/15	ASTM B209	B	N											

MSFC-HDBK-527 REV F 9999942 0004942 4

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52187	AL 7178-O TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	N											
52956	AL 7178-O TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	N											
52183	AL 7178-O WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	N											
52223	AL 7178-O WIRE RIVET AND COLD HEADING SPEC: ASTM B316		B	N											
52190	AL 7178-T6 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	C											
52182	AL 7178-T6 PLATE SPEC: QQ-A-250/14D		B	C											
52477	AL 7178-T6 PLATE CLAD SPEC: ASTM B209	QQ-A-250/15	B	B	A		A	A		A		A	A		
52189	AL 7178-T6 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	C											
52228	AL 7178-T6 ROD RIVET AND COLD HEADING SPEC: ASTM B316		B	B											
52191	AL 7178-T6 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	C											
52176	AL 7178-T6 SHEET SPEC: ASTM B209	QQ-A-250/14D	B	B											
30158	AL 7178-T6 SHEET CLAD SPEC: ASTM B209	QQ-A-250/15	B	C	A		A	A		U		A	A		
52614	AL 7178-T6 SHEET CLAD W/7011 SPEC: QQ-A-250/28		B	B											
52192	AL 7178-T6 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	B											
52957	AL 7178-T6 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
52188	AL 7178-T6 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	B											
52225	AL 7178-T6 WIRE RIVET AND COLD HEADING SPEC: ASTM B316		B	B											

MSFC-HDBK-527 REV F 9999942 0004943 6

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52205	AL 7178-T62 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	C											
52178	AL 7178-T62 PLATE SPEC: ASTM B209		B	C											
52479	AL 7178-T62 PLATE CLAD SPEC: ASTM B209	QQ-A-250/15	B	C											
52204	AL 7178-T62 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	C											
52206	AL 7178-T62 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	C											
52177	AL 7178-T62 SHEET SPEC: ASTM B209		B	B											
52478	AL 7178-T62 SHEET CLAD SPEC: ASTM B209	QQ-A-250/15	B	B											
52615	AL 7178-T62 SHEET CLAD W/7011 SPEC: QQ-A-250/28		B	B											
52207	AL 7178-T62 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	B											
52960	AL 7178-T62 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
52203	AL 7178-T62 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	B											
52179	AL 7178-T651 PLATE SPEC: ASTM B209	QQ-A-250/14D	B	C											
52616	AL 7178-T651 PLATE CLAD W/7011 SPEC: QQ-A-250/28		B	C											
52480	AL 7178-T651 PPLATE CLAD SPEC: ASTM B209	QQ-A-250/15	B	C											
52195	AL 7178-T6510 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	C											
52194	AL 7178-T6510 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	C											
52196	AL 7178-T6510 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	C											

MSFC-HDBK-527 REV F 9999942 0004944 8

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52197	AL 7178-T6510 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	B											
52958	AL 7178-T6510 TUBE EXTRUDED SEAMLESS SPEC: ASTM B241		B	B											
52193	AL 7178-T6510 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	B											
52200	AL 7178-T6511 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	C											
52199	AL 7178-T6511 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	C											
52201	AL 7178-T6511 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	C											
52202	AL 7178-T6511 TUBE EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	B											
52959	AL 7178-T6511 TUBE EXTRUDED SEAMLESS		B	B											
52198	AL 7178-T6511 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/13B	B	B											
52210	AL 7178-T76 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/14	B	B											
52209	AL 7178-T76 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/14	B	B											
52211	AL 7178-T76 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/14	B	B											
52180	AL 7178-T76 SHEET SPEC: ASTM B209	QQ-A-250/21	B	A											
52481	AL 7178-T76 SHEET CLAD SPEC: ASTM B209	QQ-A-250/22	B	A											
52617	AL 7178-T76 SHEET CLAD W/7011 SPEC: QQ-A-250/28		B	A											
52212	AL 7178-T76 TUBE EXTRUDED SPEC: ASTM B221		B	A											
52208	AL 7178-T76 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/14	B	A											
52181	AL 7178-T7651 PLATE SPEC: ASTM B209	QQ-A-250/21	B	B											

MSFC-HDBK-527 REV F 9999942 0004945 T

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52482	AL 7178-T7651 PLATE CLAD SPEC: ASTM B209	QQ-A-250/22	B	B											
52618	AL 7178-T7651 PLATE CLAD W/7011 SPEC: QQ-A-250/28		B	B											
52215	AL 7178-T76510 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/14	B	B											
52214	AL 7178-T76510 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/14	B	B											
52216	AL 7178-T76510 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/14	B	B											
52217	AL 7178-T76510 TUBE EXTRUDED SPEC: ASTM B221		B	A											
52213	AL 7178-T76510 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/14	B	A											
52220	AL 7178-T76511 BAR EXTRUDED SPEC: ASTM B221	QQ-A-200/14	B	B											
52219	AL 7178-T76511 ROD EXTRUDED SPEC: ASTM B221	QQ-A-200/14	B	B											
52221	AL 7178-T76511 SHAPES EXTRUDED SPEC: ASTM B221	QQ-A-200/14	B	B											
52222	AL 7178-T76511 TUBE EXTRUDED SPEC: ASTM B221		B	A											
52218	AL 7178-T76511 WIRE EXTRUDED SPEC: ASTM B221	QQ-A-200/14	B	A											
50675	AL 7178-T76XX PLATE CLOSE TOLERANCE SPEC: MB0170-078	QQ-A-250/21	B	B											
10238	AL 7178-T76XX SHEET CLOSE TOLERANCE SPEC: MB0170-078	QQ-A-250/21	B	A	A	1000	A	A		X		A	A		
51562	AL 7475-T61 SHEET SPEC: AMS 4084		B	B											
50992	AL 7475-T61 SHEET CLAD SPEC: AMS 4207		B	B											
51564	AL 7475-T651 PLATE SPEC: AMS 4090		B	C											

MSFC-HDBK-527 REV F ■ 9999942 0004946 1 ■

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51566	AL 7475-T7351 PLATE SPEC: AMS 4202	B	A											
51563	AL 7475-T761 SHEET SPEC: AMS 4085	B	A											
51565	AL 7475-T7651 PLATE SPEC: AMS 4089	B	B											
50676	AL 800 SPHERES	B	U											
51178	AL 8017	B	U											
51177	AL 8030	B	U											
51188	AL 8176	B	U											
51176	AL 8177	B	U											
50204	AL 99 F-11 (RIVET) SPEC: RBO170-236	U	U											
52483	AL A140	B	U											
52485	AL A142	B	U											
52938	AL A201.0-T4 CASTINGS PERMANENT MOLD SPEC: MIL-A-21180D	B	U											
52939	AL A201.0-T4 CASTINGS SAND (WITH CHILLS) SPEC: MIL-A-21180D	B	U											
50979	AL A201.0-T4 CASTINGS SPECIAL MOLD	B	U											
50980	AL A201.0-T7 CASTINGS SPEC: MIL-A-21180D	B	U											
52940	AL A201.0-T7 CASTINGS PERMANENT MOLD SPEC: MIL-A-21180D	B	U											
52941	AL A201.0-T7 CASTINGS SAND SPEC: MIL-A-21180D	B	U											
52937	AL A201.0-T7 CASTINGS SPECIAL MOLD SPEC: MIL-A-21180D	B	U											
52488	AL A218-F CASTINGS SAND	B	A											
10485	AL A356.0-T51 CASTING SPEC: AMS 4261	B	A	A	1000	A	A		A		A	A		

MSFC-HDBK-527 REV F ■ 9999942 0004947 3 ■

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50060	AL A356.0-T6 CASTING INVESTMENT SPEC: MIL-A-21180	B	A	A		A	A		A		U	U		
51045	AL A356.0-T6 CASTINGS SPEC: MIL-A-21180D	B	A	A		A	A		A		U	U		
10053	AL A356.0-T61 CASTINGS SPEC: AMS 4218 MIL-A-21180	B	A	A	1000	A	A		A		A	A		
52950	AL A357.0-T6 CASTINGS INSULATED MOLD	B	A											
52951	AL A357.0-T6 CASTINGS PERMANENT MOLD SPEC: MIL-A-21180D	B	A											
50985	AL A357.0-T6 CASTINGS SAND SPEC: MIL-A-21180D	B	A											
52952	AL A357.0-T6 CASTINGS SPECIAL MOLD SPEC: MIL-A-21180D	B	A											
50986	AL A357.0-T61 CASTINGS SPEC: MIL-A-21180D	B	A											
52954	AL A357.0-T61 CASTINGS PERMANENT MOLD SPEC: MIL-A-21180D	B	A											
52953	AL A357.0-T61 CASTINGS SAND SPEC: MIL-A-21180D	B	A											
52955	AL A357.0-T61 CASTINGS SPECIAL MOLD SPEC: MIL-A-21180D	B	A											
10613	AL A360-F CASTINGS DIE SPEC: QQ-A-591	B	U	A		A	A		A		A	A		
10396	AL A380 CASTINGS DIE SPEC: QQ-A-591	B	A	A		A	A		A		A	A		
52490	AL ALMAG-35-F CASTINGS SAND	B	A											
52487	AL B195	B	C											
52908	AL B218-F CASTINGS SAND	B	A											
10329	AL BRONZE #606 FORGING 70 KSI SPEC: QQ-C-465	A	A	A		A	X		X		A	U		
50677	AL BRONZE #614 FORGING 70 KSI SPEC: QQ-C-465	A	U	A		A	X		X		A	U		
10376	AL BRONZE #623 BAR SPEC: AMS 4635	A	A	A		A	X		X		A	U		

MSFC-HDBK-527 REV F 9999942 0004948 5

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50680	AL BRONZE #623 FORGING SPEC: AMS 4635		A	A	A		A	X		X		A	U		
50681	AL BRONZE #630 BAR 110 KSI SPEC: AMS 4640		A	A	A		A	X		X		A	U		
10258	AL BRONZE #630 CASTINGS BEARING 95 KSI SPEC: AMS 4880		A	A	A		A	X		X		A	U		
50682	AL BRONZE #630 FORGING 110 KSI SPEC: AMS 4640		A	A	A		A	X		X		A	U		
50678	AL BRONZE #630 FORGING 70 KSI		A	A	A		A	X		X		A	U		
10257	AL BRONZE #630 ROD 110 KSI SPEC: AMS 4640	QQ-C-390	A	A	A	1000	A	X		X		A	A		
10410	AL BRONZE #637 SPEC: AMS 4631	QQ-C-465	A	A	A		A	X		X		A	U		
50712	AL BRONZE #639 SPEC: AMS 4631	QQ-C-465	A	A	A		A	X		X		A	U		
50679	AL BRONZE #642 FORGING 70 KSI SPEC: QQ-C-465		B	A	A		A	X		X		A	U		
10395	AL C355.0-T6 CASTING SPEC: AMS 4215	MIL-A-21180	B	A	A		A	A		A		A	A		
52871	AL C355.0-T61 CASTINGS PERMANENT MOLD SPEC: MIL-A-21180C		B	A	A		A	A		A		A	A		
10664	AL CASTING 99.75% ALUMINUM MANF: REYNOLDS METAL CO		B	A	A		A	A		A		A	A		
51168	AL KO-1 CASTINGS PREMIUM SPEC: ESPD 102A		B	U											
51167	AL KO-1 CASTINGS SAND SPEC: ESPD 101A		B	U											
51223	AL KO-1-T6 CASTINGS		B	U											
51224	AL KO-1-T7 CASTINGS SPEC: AMS 4229		B	U											
10252	AL SHIM STOCK (COMP 1) SPEC: MIL-S-22499		B	A	X		A	X		A		A	A		
50184	AL TENS-50 CASTING SPEC: RB0170-008	RB0170-099	B	A	A		A								

MSFC-HDBK-527 REV F 9999942 0004949 7

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50978	AL X5090		B	U											
50683	AM 350 SCT 100 STRIP SPEC: AMS 5548	MIL-S-8840	A	A	A		A	A		A		A	A		
10738	AM 350 SCT 1000 SHEET SPEC: AMS 5548	MIL-S-8840	A	A	A		A	A		A		A	U		
10207	AM 350 SCT 850 SHEET SPEC: AMS 5548	MIL-S-8840	A	C	A		A	A		A		A	U		
50684	AM 350 SCT 850 STRIP SPEC: AMS 5548		A	C	A		A	A		A		A	U		
50685	AM 355 SCT 1000 BAR		A	A	A		A	A		A		A	U		
10085	AM 355 SCT 1000 FORGING SPEC: AMS 5743		A	A	A		A	A		A		A	U		
30195	AMERICIUM-241		A	A	U		U	U		U		U	U		
50689	BE 2% BEO BAR SPEC: MB0170-055		A	U											
50691	BE 2% BEO EXTRUSIONS SPEC: MB0170-055		A	U											
50690	BE 2% BEO FORGING SPEC: MB0170-055		A	U											
50688	BE 2% BEO PLATE SPEC: MB0170-055		A	U	A	1000	A	A		U		A	A		
30044	BE 2% BEO SHEET SPEC: MB0170-055		A	U	A	1000	A	A		U		A	A		
30131	BE BRAKEGRADE ES13.3.19		B	U	U		U	U		U		U	U		
50136	BE-CU #10 SPEC: MIL-C-81021		A	A	A		A	U		U		U	U		
50304	BE-CU #170 MANF: CERTANIUM SPEC: QQ-C-533		A	A	A		A	X		X		A	A		
10256	BE-CU #172 WIRE CONDITION A SPEC: QQ-C-533		A	A	A	1000	A	X		X		A	A		
10271	BE-CU #173 BAR SPEC: QQ-C-530		A	A	A	1000	A	X		X		A	A		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0004950 3

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50961	BE-CU #173 ROD SPEC: QQ-C-530		A	A	A	1000	A	X		X		A	A		
50962	BE-CU #173 WIRE SPEC: QQ-C-530		A	A	A	1000	A	X		X		A	A		
10638	BE-CU #175 SPEC: ASTM B194 MIL-C-81021	CU96 BE.6 CO2.6	A	A	A		A	X		X		A	A		
10716	BE-CU #175 BAR SPEC: ASTM B 534		A	A	A		A	X		X		A	A		
50960	BE-CU #175 PLATE SPEC: ASTM B534		A	A	A		A	X		X		A	A		
50959	BE-CU #175 SHEET SPEC: ASTM B534		A	A	A		A	X		X		X	X		
10149	BE-CU #175 WIRE CONDITION A SPEC: ASTM B534		A	A	A	1000	A	X		X		A	A		
10467	BE-CU CASTING MANF: ARMCO SPEC: QQ-C-390		A	A											
10741	BERYLCO 440		A	U	A		A	A		X		U	U		
10709	BERYLLIUM BAR SPEC: AMS 7901		A	A	A		A	A		U		A	A		
52426	BERYLLIUM RODS		A	A	A		A	A		U		A	A		
52427	BERYLLIUM SHAPES		A	A	A		A	A		U		A	A		
50134	BIMETAL THERMOSTATIC		A	U	U		U	U		U		U	U		
30097	BORON/AL 6061 TUBE ANNEALED MANF: CONVAIR		B	A	A		A	A		X		A	A		
50310	BRASS BAR SPEC: QQ-B-626		B	B	A		A	X		X		U	U		
10234	BRASS SHIM STOCK >1/8HD COMP 2 SPEC: MIL-S-22499		A	A	A	3300	A	X		X		U	U		
50692	BRASS STRIP SPEC: QQ-B-626		B	B	A		A	X		X		U	U		
10321	BRASS,ALL FORM SPEC: ASTM B-124 ASTM B-36 QQ-B-613 QQ-B-637	ASTM B-16 ASTM B-453 QQ-B-626	B	B	A	3300	A	X		X		A	A		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0004951 5

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10462	BRAZE 20AG 45CU 35ZN ALLOY 202 SPEC: QQ-B-654 GR-0		A	N	A		A	X		X		U	U		
10459	BRAZE 40AG 30CU 28ZN 2NI		A	N	A		A	X		X		U	U		
10364	BRAZE 45 AG 15 CU 16 ZN 24 CD SPEC: QQ-B-654		A	N	A	1000	A	X		X		A	A		
50196	BRAZE 46RI.35AU 14NI 10PD9.5MN		A	N	U		U	U		U		U	U		
50197	BRAZE 49RI.31AU 10PD 10NI 16MN		A	N	U		U	U		U		U	U		
50105	BRAZE 50AG 15.5CU 15.5ZN 16CD		A	N	A		A	X		X		U	U		
10710	BRAZE 50AG 15CU 16ZN 20CD SPEC: QQ-B-654		A	N	A		A	X		X		U	U		
10728	BRAZE 50AG 16CU 15ZN 3NI SPEC: QQ-S-561 CL5		A	N	A		A	X		X		U	U		
50195	BRAZE 50AU 25NI 25PD		U	N	U		U	U		U		U	U		
10481	BRAZE 50CO 8SI 19CR 17NI 4W.8B SPEC: AMS 4783		A	N	U		U	U		U		U	U		
10197	BRAZE 52.5CU 38.5MN 9NI SPEC: AMS 4764		A	N	U		U	U		U		A	A		
10624	BRAZE 54AG 40CU 5ZN 1NI SPEC: AMS 4772	QQ-B-654 BAG-13	A	N	U		U	U		U		U	U		
10463	BRAZE 55AU 25AG 15PD 5PT		A	N	U		A	U		U		U	U		
10458	BRAZE 56AG 22CU 17ZN 5SN SPEC: QQ-B-654 BAG-7		A	N	A		A	X		X		A	U		
10650	BRAZE 56AG 42CU 2NI SPEC: AMS 4765	QQ-B-654 BAG-13	A	N	A		A	X		C		A	A		
10242	BRAZE 60AG 30CU 10SN SPEC: AMS 4773	BAG-18	A	N	X		A	X		X		U	U		
10200	BRAZE 62.5AG 32.5CU 5NI SPEC: MB0170-037		A	N	A		A	X		X		A	A		
10243	BRAZE 63AG 28.5CU 6SN 2.5NI SPEC: AMS 4774		A	N	X		A	X		X		U	U		
10429	BRAZE 65AG 20CU 15ZN SPEC: QQ-B-654 BAG-9		A	N	A	1000	A	X		X		U	U		

MSFC-HDBK-527 REV F 9999942 0004952 7

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10326	BRAZE 66NI 12MN 7SI 5CU (AMBRY930 MANF: ALLOY METALS INC SPEC: MB0170-095		A	N	U		U	U		X		C	X		
10478	BRAZE 70AU 8PD 22NI SPEC: AMS 4786		A	N	U		U	U		U		U	U		
10198	BRAZE 72AU 22NI 6CR SPEC: MB0170-019		A	N	A	1600	A	U		X		A	A		
10245	BRAZE 73NI 4.5SI 14CR 3.1B4.5 SPEC: AMS 4775	BNI-1	A	N	A	1600	A	A		X		A	X		
50199	BRAZE 75AG 20PD 5MN		A	N	U		U	U		U		U	U		
10461	BRAZE 75AG 25ZN		A	N	X		A	X		X		U	U		
50194	BRAZE 75AU 20CU 5AG >200KSI		A	N	U		U	U		U		U	U		
10196	BRAZE 81.5AU 16.5CU 2.0NI SPEC: MB0170-014		A	N	A	9999	A	X		X		A	A		
10119	BRAZE 82AU 18NI SPEC: AMS 4787 MIL-S-7420	BAU-4	A	N	A	3000	A	X		X		A	A		
10479	BRAZE 82NI 4.5SI 7CR 3FE 3.1B SPEC: AMS 4777	BNI-2	A	N	U		U	U		U		U	U		
50200	BRAZE 90AG 10PD		A	N	U		U	U		U		U	U		
10339	BRAZE 92.5 AG 7.2 CU .22 LI SPEC: AMS 4767	BAG-19	A	N	A		A	X		X		U	U		
10246	BRAZE 92NI 4.5SI 3.1B SPEC: AMS 4778	BNI-3	A	N	A	1600	A	X		X		A	X		
10705	BRAZE 99.9 AU		A	N	A		A	X		X		A	A		
10493	BRAZE AG-PLATIUM		A	N	U		U	U		U		U	U		
10244	BRAZE AG15 80CU 5P SPEC: QQ-B-654 CL III		A	N	A	2700	A	X		X		U	U		
10721	BRAZE AL ALLOY 10SI 1.2MN SPEC: ALCOA 23F	HS 5873 CL2	A	N	A		A	A		A		A	A		
10440	BRAZE AL ALLOY 4047 SPEC: ALCOA 718		B	N	A		A	A		A		A	A		
10434	BRAZE AL ALLOY 4145 WIRE SPEC: AMS 4184		B	N	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004953 9

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
30186	BRAZE AL#21-O SHEET (CL ONE SIDE SPEC: AMS 4054		B	N	A		A	A		A		A	A		
30185	BRAZE AL#22-O SHEET 2-SIDES CLAD SPEC: AMS 4055		B	N	A		A	A		A		A	A		
50236	BRAZE ALLOY #8 3NI 62CU 35AU		A	N	U		U	U		U		U	U		
10673	BRAZE BNI-4 94NI 3.5SI 1.8B SPEC: AMS 4779		A	N	A		A	X		X		A	X		
10460	BRAZE BNI-6 11NI .015C		A	N	A		A	X		A		U	U		
10248	BRAZE COPPER FLAT RODS SPEC: QQ-C-502		A	N	A	3000	A	X		X		U	U		
50693	BRAZE COPPER FLAT SHAPES SPEC: QQ-C-502		A	N	A		A	X		X		U	U		
50210	BRAZE DEGUSSA 5400														
10480	BRAZE EASY-FLO 45 SPEC: AMS 4769	AMS 4770	A	N	U		U	U		U		U	U		
10247	BRAZE ELEC COPPER UNINSULATED SPEC: QQ-W-343		A	N	A	2700	A	X		X		U	U		
10657	BRAZE LITHOBRAZE MANF: HANDY HARMAN		A	N	A		A	X		X		U	U		
10199	BRAZE LTC 80/20 NI MATRIX SPEC: MB0170-036		A	N	A	1000	A	X		X		A	A		
10523	BRAZE NEYORO AU-AG ALLOYS MANF: JM NEY CO SPEC: ASTM B 477		A	N	U		U	U		U		U	U		
10714	BRAZE NEYORO AU-PT-AG-CU ALLOY MANF: J M NEY CO SPEC: MIL-E-46065		A	N	U		U	U		U		U	U		
10604	BRAZE PERMABRAZE 615 MANF: HANDY AND HARMAN		A	N	U		U	U		U		U	U		
10651	BRAZE WILBRAZE 6022 MANF: WILKINSON CO		A	N	A		A	X		X		A	A		
10418	BRONZE 60.5CU 3MN BAL ZN ROD SPEC: SAE J463A		B	B	A	2600	A	X		X		U	U		
50186	BRONZE 70CU 10SN 20PB		B	A	X		A	X		X		A	C		

MSFC-HDBK-527 REV F 9999942 0004954 0

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZK RTG	HDZK TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50311	BRONZE BAR		B	A	A		A	X		X		A	C		
10656	BRONZE CASTING CA 922 SPEC: ASTM B 61		B	B	A		A	X		X		A	C		
50103	BRONZE MESH 40-50 MICRONS-FILTER SPEC: MS51607		B	U	U		U	U		U		U	U		
10619	BRONZE OILITE 10SN		B	U	X		A	X		X		A	C		
10360	BRONZE PHOSPHOR SAE 660 SPEC: ASTM-B584 QQ-C-390 ALY E7	QQ-C-390	B	A	A	1000	A	X		X		A	C		
10322	BRONZE PHOSPHOR-ALL FORMS SPEC: ASTM B-103 BERIUM METAL QQ-W-321	ASTM B-139 QQ-B-750 SAE 64	B	A	A		A	X		X		A	C		
50694	BRONZE PLATE SPEC: QQ-B-750		B	A	U		U	U		U		U	U		
50695	BRONZE SHEET SPEC: QQ-B-750		B	A	U		U	U		U		U	U		
50106	BRONZE SINTER		B	U	U		U	U		U		U	U		
50696	BRONZE STRIP SPEC: QQ-B-750		B	A	U		U	U		U		U	U		
50697	BRONZE WIRE SPEC: QQ-B-750		B	A	U		U	U		U		U	U		
10602	BRONZE,TELNIC (99.9% CU) SPEC: ASTM-B-3-1		A	A	A		A	X		X		A	A		
50506	CABLE CLAMP AL 6061-T6		B	A	U		U	U		U		U	U		
50143	CABLE ELECTRICAL SPEC: MIL-C-27500		U	U	U		U	U		U		U	U		
10660	CB 103 BAR ANNEALED SPEC: HM STD SVHS7204		A	U	X		A	U		U		U	A		
50703	CB 103 PLATE		A	U	X		A	U		U		U	A		
30163	CB 103 SHEET		A	U	X		A	U		U		U	U		
50702	CB 103 SHEET ANNEALED SPEC: SVHS 7204		A	U	X		A	U		U		U	U		

MSFC-HDBK-527 REV F ■ 9999942 0004955 2 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
30051	CB 752 SHEET ANNEALED SPEC: MB0170-068		A	U	A		A	U		U		U	U		
50704	CB 752 STRIP ANNEALED SPEC: MB0170-068		A	U	A		A	U		U		U	U		
50700	CB BAR SPEC: ASTM B-392		A	U	X		A	U		U		U	U		
10719	CB C-103 BAR INGOT SPEC: MB0170-104 CL 1	MB0170-104 CL 2	A	U	U		U	U		U		U	U		
30052	CB C129Y SHEET ANNEALED SPEC: MB0170-038		A	U	A		A	A		A		U	U		
50698	CB C129Y STRIP ANNEALED SPEC: MB0170-038		A	U	A		A	A		A		U	U		
50699	CB FS 85 PLATE		A	U	A		A	A		A		U	U		
30053	CB FS 85 SHEET		A	U	A		A	A		A		U	U		
30129	CB ROD SPEC: ASTM B 392		A	U	X		A	U		U		U	U		
50701	CB WIRE SPEC: ASTM B-392		A	U	X		A	U		U		U	U		
10724	CB-1ZR MANF: WAH CHANG SPEC: WC-1ZR		A	U	U		U	U		U		U	U		
50507	CLAMP CABLE AL 2024-T4 MANF: BENDIX ELECT COMPNTS SPEC: MIL-C-27599		B	C	U		U	U		U		U	U		
10707	CO BASE 32CR 18W 2.6C STAR J PM MANF: HAYNES STELLITE		A	U	U		U	A		A		U	U		
10472	COATING AL PLASMA SPEC: MA0109-308		B	N	A		A	A		A		A	A		
10276	COATING ANODIC SPEC: MIL-A-8625		A	N	A	3000	A	A		X		A	A		
10743	COATING ANODIC DOW 17 SPEC: MIL-M-45202		A	N	U		U	U		U		U	U		
10640	COATING ANODIC T1 SPEC: MIL-A-8625		A	N	U		U	U		U		U	U		

MSFC-HDBK-527 REV F 9999942 0004956 4

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10277	COATING ANODIC T2 SPEC: MIL-A-8625		A	N	A	3000	A	A		X		A	A		
10283	COATING ANODIC T3 HARD SPEC: MIL-A-8625		A	N	A	1300	A	A		A		A	A		
10649	COATING ANODIC TIODIZE SPEC: AMS 2488		A	N	A		A	U		U		U	U		
30119	COATING ANODIZING, BERYLLIUM SPEC: MAO109-310		B	N	U		U	U		U		U	U		
30194	COATING FERRIC FEO.FE203		A	N	A		A	U		U		A	U		
10717	COATING PLASMA SPRAY DEPOSITED SPEC: AMS 2437		A	N	A		U	A		X		U	X		
50837	COPPER 100% PLATE ANNEALED SPEC: ASM 4500	MIL-W-85/1	A	A	A	2700	A	X		X		A	A		
10213	COPPER 100% SHEET ANNEALED		A	A	A	2700	A	X		X		A	A		
50838	COPPER 100% STRIP ANNEALED		A	A	A	2700	A	X		X		A	A		
10615	COPPER 22NI		A	A	U		U	U		U		U	U		
10607	COPPER 30NI ALLOY NO 715 SPEC: ASTM-B-122 #5		A	A	U		U	U		U		U	U		
10623	COPPER 3NI WIRE		A	A	U		U	U		U		U	U		
10685	COPPER 55 18NI 27ZN ALLOY 770 SPEC: ASTM B122 #4		B	C	U		U	U		U		U	U		
10614	COPPER 6%NI		A	A	U		U	U		U		U	U		
10372	COPPER 62CU CDA350 BRASS COPPER SPEC: ASTM B121 MRC-MS988	ASTM B453	A	C	A		A	X		X		A	A		
50841	COPPER 63 ZN37 ROD SPEC: DIN 1756	DIN 17660	U	C	U		U	U		U		U	U		
50244	COPPER 63 ZN37 SHEET SPEC: DIN 1756	DIN 17660	U	C	U		U	U		U		U	U		
10715	COPPER 65 18NI 17ZN ALLOY 752 SPEC: QQ-C-585		A	C	A		A	X		X		A	A		
50839	COPPER 661/SIL ALLOY BAR SPEC: ASTM B-98		A	A	U		U	U		U		U	U		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0004957 6

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50504	COPPER 661/SIL ALLOY ROD SPEC: ASTM B98		A	A	U		U	U		U		U	U		
50840	COPPER 661/SIL ALLOY SHAPE SPEC: ASTM B-98		A	U	U		U	U		U		U	U		
50190	COPPER 96 3AG NARLOY Z SPEC: RB0170-175	RB0170-236	U	U	U		U	U		U		U	U		
10620	COPPER 97.8 1PB 1NI .2P		A	A	A		A	X		X		A	A		
50111	COPPER ALLOY		A	N											
10354	COPPER ALLOY 102 WIRE SPEC: AMS 4701 ASTM B3	ASTM B170 QQ-W-343	A	A	A		A	X		X		A	A		
50829	COPPER ALLOY 110 BAR SPEC: ASTM B-152	ASTM B-187	A	A	A		A	X		X		U	U		
50827	COPPER ALLOY 110 PLATE SPEC: ASTM B-152	ASTM B-187	A	A	A		A	X		X		U	U		
50828	COPPER ALLOY 110 ROD SPEC: ASTM B-152	ASTM B-187	A	A	A		A	X		X		X	X		
10346	COPPER ALLOY 110 SHEET SPEC: ASTM B152 MIL-F-55561	ASTM B187	A	A	A		A	X		X		U	U		
50826	COPPER ALLOY 110 STRIP SPEC: ASTM B-152	ASTM B-187	A	A	A		A	X		X		U	U		
50144	COPPER ALLOY 210 (95%) SHEET SPEC: MIL-C-21768		A	A	U		U	U		U		U	U		
50830	COPPER ALLOY 210 (95%) STRIP SPEC: MIL-C-21768		A	A	U		U	U		U		U	U		
50303	COPPER ALLOY 220 (90%) SHEET MANF: CERTANIUM SPEC: MIL-C-21768		A	A	U		U	U		U		A	A		
50831	COPPER ALLOY 220 (90%) STRIP SPEC: MIL-C-21768		A	A	U		U	U		U		U	U		
10634	COPPER ANACONDA # 1870		A	U	A	3000	A	X		X		A	A		
10333	COPPER BAR ANNEALED HARD TEMPER SPEC: AMS 4602 ASTM B-301 QQ-C-502	ASTM B-152 QQ-C-501 QQ-C-576	A	A	A		A	X		X		A	A		

MSFC-HDBK-527 REV F 9999942 0004958 8

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	MDEE RTG	MDEE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10317	COPPER BAR BUS TYPE 1 SPEC: QQ-B-825		A	A	A		A	X		X		A	A		
50285	COPPER FOIL 99.75CU		A	A	A		A	X		X		X	A		
50193	COPPER HARLOY A SPEC: RB0170-163	RB0170-236	U	U	U		U	U		U		A	A		
10621	COPPER PD-135 99.2CU .4CD .4CR		A	A	U		U	U		U		A	A		
50832	COPPER ROD ANNEALED HARD TEMPER SPEC: AMS 4602 QQ-C-576	QQ-C-501	A	A	A		A	X		X		A	A		
50834	COPPER ROD BUS TYPE 1 SPEC: QQ-B-825		A	A	A			X		X		A	A		
10501	COPPER RODS SPEC: QQ-C-502 QQ-C-576	QQ-C-504 WW-T-799	A	A	A		A	X		X		A	A		
50295	COPPER SE F-20		A	U	A		A	X		X		X	U		
50836	COPPER SHAPES SPEC: QQ-B-825 QQ-C-576	QQ-C-502 WW-T-799	A	A	A		A	X		X		A	A		
50833	COPPER SHAPES ANNEALED HARD TEMPER SPEC: AMS 4602 MIL-F-55561 QQ-C-576	ASTM B-301 QQ-C-501	A	A	A		A	X		X		A	A		
50835	COPPER SHAPES BUS TYPE 1 SPEC: QQ-B-825		A	A	A		A	X		X		A	A		
10698	COPPER SILICON-BRONZE ALLOY # 655 SPEC: QQ-C-591		A	A	A		A	X		X		A	A		
50114	COPPER TERMINAL LUG SPLICE SPEC: MIL-T-7928														
10353	COPPER TUBE ANNEALED NI PLATED SPLICE SPEC: ASTM B280		A	A	A		A	A		X		A	A		
10483	COPPER TUBE SEAMLESS SPEC: ASTM B75	WW-T-799	A	A	A		A	X		X		A	A		
10439	COPPER WIRE (RIVETS) SPEC: QQ-W-343		A	A	A		A	X		X		A	A		
10469	COPPER WIRE AG PLATE SOFT OR ANN SPEC: ASTM B 298 MIL-W-16878/13 MIL-W-16878/5	MIL-W-16878/11 MIL-W-16878/4 MIL-W-16878/6	A	N	A		A	X		X		A	A		

MSFC-HDBK-527 REV F 9999942 0004959 T

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10352	COPPER WIRE AU PLATE ELECTRO DEPOSITED	A	N	A		A	X		X		A	A		
50068	COPPER WIRE FABRIC STEEL WELDED SPEC: MIL-W-585T2C105	A	A	U		U	X		X		A	A		
10642	COPPER WIRE NI ELECTRICAL CLAD SPEC: MIL-W-25038/1B MIL-W-25038/2B	A	A	U		U	U		U		A	A		
53143	CRES 12.5CR-1W BAR ANNEALED & TEMPERED SPEC: AMS 5655	A	A											
53144	CRES 12.5CR-1W FORGING ANNEALED & TEMPERED	A	A											
53145	CRES 12.5CR-1W FORGING STOCK ANNEALED & TEMPERED SPEC: AMS 5655	A	A											
53260	CRES 12CR FERRITE CONTROLLED BAR QUENCHED & TEMPERED SPEC: AMS 5611 AMS 5612	A	A											
53261	CRES 12CR FERRITE CONTROLLED FORGING QUENCHED & TEMPERED SPEC: AMS 5611 AMS 5612	A	A											
53263	CRES 12CR FERRITE CONTROLLED FORGING STOCK QUENCHED & TEMPERED SPEC: AMS 5611 AMS 5612	A	A											
53259	CRES 12CR FERRITE CONTROLLED PLATE ANNEALED SPEC: AMS 5505 AMS 5609	A	A											
53257	CRES 12CR FERRITE CONTROLLED SHEET ANNEALED SPEC: AMS 5505 AMS 5609	A	A											
53258	CRES 12CR FERRITE CONTROLLED STRIP ANNEALED SPEC: AMS 5505 AMS 5609	A	A											
53262	CRES 12CR FERRITE CONTROLLED TUBE QUENCHED & TEMPERED SPEC: AMS 5611 AMS 5612	A	A											
53118	CRES 12CR-0.5MO BAR TEMPERED SPEC: AMS 5614	A	A											
53119	CRES 12CR-0.5MO FORGING TEMPERED SPEC: AMS 5614	A	A											
53120	CRES 12CR-0.5MO STOCK FORGING TEMPERED SPEC: AMS 5614	A	A											
53437	CRES 13PH-8MO A1000	A	B											
53438	CRES 13PH-8MO A1050	A	B											
53439	CRES 13PH-8MO A1100	A	B											

MSFC-HDBK-527 REV F ■ 9999942 0004960 6 ■

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53436	CRES 13PH-8MO A950	A	B											
53442	CRES 13PH-8MO BCHT950 FORGING SPEC: AMS 5629A	A	B											
53431	CRES 13PH-8MO CONDITION A	A	B											
30113	CRES 13PH-8MO H1000 BAR SPEC: AMS 5629	A	B	A		A	A		A		U	X		
53453	CRES 13PH-8MO H1000 BAR FLAT SPEC: AMS 5629A	A	B											
53451	CRES 13PH-8MO H1000 BAR HEX SPEC: AMS 5629A	A	B											
53450	CRES 13PH-8MO H1000 BAR ROUND SPEC: AMS 5629A	A	B											
53452	CRES 13PH-8MO H1000 BAR SQUARE SPEC: AMS 5629A	A	B											
53473	CRES 13PH-8MO H1000 EXTRUSIONS	A	B											
50713	CRES 13PH-8MO H1000 FORGING SPEC: AMS 5629	A	B	A		A	A		A		U	X		
53445	CRES 13PH-8MO H1000 PLATE	A	B											
53472	CRES 13PH-8MO H1000 RINGS FLASH WELDED SPEC: AMS 5629A	A	B											
53441	CRES 13PH-8MO H1000 SHEET	A	B											
53485	CRES 13PH-8MO H1000 STRIP	A	B											
10343	CRES 13PH-8MO H1025 BAR SPEC: AMS 5629	A	B	A	3300	A	A		A		U	X		
53457	CRES 13PH-8MO H1025 BAR FLAT SPEC: AMS 5629A	A	B											
53455	CRES 13PH-8MO H1025 BAR HEX SPEC: AMS 5629A	A	A											
53454	CRES 13PH-8MO H1025 BAR ROUND SPEC: AMS 5629A	A	B											
53456	CRES 13PH-8MO H1025 BAR SQUARE SPEC: AMS 5629A	A	B											

MSFC-HDBK-527 REV F 9999942 0004961 8

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53475	CRES 13PH-8MO H1025 EXTRUSIONS	A	B											
50714	CRES 13PH-8MO H1025 FORGING SPEC: AMS 5629	A	B	A		A	A		A		U	X		
53474	CRES 13PH-8MO H1025 RINGS FLASH WELDED SPEC: AMS 5629A	A	B											
10285	CRES 13PH-8MO H1050 BAR MANF: ZZ 01 10147 ZZ HDZE 10147 ZZ N2O4 10264 SPEC: AMS 5629	A	B	A	3300	A	A		A		U	X		
53461	CRES 13PH-8MO H1050 BAR FLAT SPEC: AMS 5629A	A	B											
53459	CRES 13PH-8MO H1050 BAR HEX SPEC: AMS 5629A	A	B											
53458	CRES 13PH-8MO H1050 BAR ROUND SPEC: AMS 5629A	A	B											
53460	CRES 13PH-8MO H1050 BAR SQUARE SPEC: AMS 5629A	A	B											
53477	CRES 13PH-8MO H1050 EXTRUSIONS	A	B											
50718	CRES 13PH-8MO H1050 FORGING SPEC: AMS 5629	A	B	A		A	A		A		U	X		
53476	CRES 13PH-8MO H1050 RINGS FLASH WELDED SPEC: AMS 5629A	A	B											
53486	CRES 13PH-8MO H1050 STRIP	A	B											
10344	CRES 13PH-8MO H1100 BAR SPEC: AMS 5629	A	B	A	3300	A	A		A		U	X		
53465	CRES 13PH-8MO H1100 BAR FLAT SPEC: AMS 5629A	A	B											
53463	CRES 13PH-8MO H1100 BAR HEX SPEC: AMS 5629A	A	B											
53462	CRES 13PH-8MO H1100 BAR ROUND SPEC: AMS 5629A	A	B											
53464	CRES 13PH-8MO H1100 BAR SQUARE SPEC: AMS 5629A	A	B											

MSFC-HDBK-527 REV F ■ 9999942 0004962 T ■

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53480	CRES 13PH-8MO H1100 EXTRUSIONS	A	B											
50715	CRES 13PH-8MO H1100 FORGING SPEC: AMS 5629	A	B	A		A	A		A		U	X		
53478	CRES 13PH-8MO H1100 FORGING SPEC: AMS 5629A	A	B											
53479	CRES 13PH-8MO H1100 RINGS FLASH WELDED SPEC: AMS 5629A	A	B											
10643	CRES 13PH-8MO H1150 SPEC: AMS 5629	A	B	A*	3300	A	A		A		U	X		
53434	CRES 13PH-8MO H1150 BAR SPEC: AMS 5629A	A	B											
53469	CRES 13PH-8MO H1150 BAR FLAT SPEC: AMS 5629A	A	B											
53467	CRES 13PH-8MO H1150 BAR HEX SPEC: AMS 5629A	A	B											
53466	CRES 13PH-8MO H1150 BAR ROUND SPEC: AMS 5629A	A	B											
53468	CRES 13PH-8MO H1150 BAR SQUARE SPEC: AMS 5629A	A	B											
53483	CRES 13PH-8MO H1150 EXTRUSIONS	A	B											
53481	CRES 13PH-8MO H1150 FORGING SPEC: AMS 5629A	A	B											
53435	CRES 13PH-8MO H1150M BAR SPEC: AMS 5629A	A	B											
53449	CRES 13PH-8MO H950 BAR FLAT SPEC: AMS 5629A	A	B											
53447	CRES 13PH-8MO H950 BAR HEX SPEC: AMS 5629A	A	B											
53446	CRES 13PH-8MO H950 BAR ROUND SPEC: AMS 5629A	A	B											
53448	CRES 13PH-8MO H950 BAR SQUARE SPEC: AMS 5629A	A	B											
53471	CRES 13PH-8MO H950 EXTRUSIONS	A	B											

MSFC-HDBK-527 REV F 9999942 0004963 1

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50716	CRES 13PH-8MO H950 FORGING SPEC: AMS 5629	A	B	A		A	A		A		U	X		
53443	CRES 13PH-8MO H950 PLATE	A	B											
53470	CRES 13PH-8MO H950 RINGS FLASH WELDED SPEC: AMS 5629A	A	B											
53484	CRES 13PH-8MO H950 STRIP	A	B											
53432	CRES 13PH-8MO H950 WIRE SPEC: AMS 5840	A	B											
50213	CRES 13PH-8MO H950 BAR SPEC: AMS 5629	A	B	A	3300	A	A		A		U	X		
53440	CRES 13PH-8MO ORH950	A	B											
53444	CRES 13PH-8MO PLATE WELDED & HEAT TREATED	A	B											
53433	CRES 13PH-8MO RH950 BAR SPEC: AMS 5629A	A	B											
53482	CRES 13PH-8MO RINGS FLASH WELDED SPEC: AMS 5629A	A	B											
53487	CRES 13PH-8MO STRIP WELDED AND HEAT TREATED	A	B											
53368	CRES 14PH-8MO BCHT1050 SHEET AIR MELT		A											
53384	CRES 14PH-8MO BCHT1050 SHEET CVM	A	A											
53382	CRES 14PH-8MO BCHT950 SHEET CVM	A	A											
53370	CRES 14PH-8MO CH1050 SHEET AIR MELT	A	A											
53375	CRES 14PH-8MO CH900 SHEET	A	A											
53369	CRES 14PH-8MO CH900 SHEET AIR MELT	A	A											
53376	CRES 14PH-8MO CH900 STRIP	A												
53377	CRES 14PH-8MO CH900 STRIP	A	A											
53379	CRES 14PH-8MO CH950 SHEET AIR MELT	A	A											
53378	CRES 14PH-8MO CH950 STRIP	A	A											
10081	CRES 14PH-8MO H1050 SHEET SPEC: AMS 5603	A	A	A	4500	A	A		A		U	X		

MB0160-015

MSFC-HDBK-527 REV F 9999942 0004964 3

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50719	CRES 14PH-8MO H1050 STRIP SPEC: AMS 5603	MB0160-015	A	A	A		A	A		A		U	X		
53367	CRES 14PH-8MO SHEET AIR MELT AGED		A	A											
53371	CRES 14PH-8MO SHEET CONDITION A		A	A											
53373	CRES 14PH-8MO SHEET CONDITION C		A	A											
53386	CRES 14PH-8MO SHEET CVM BRAZING-CYCLE HEAT TREATED		A	A											
53383	CRES 14PH-8MO SHEET CVM ELECTRON BEAM WELDED		A	A											
53363	CRES 14PH-8MO SRH1050 SHEET		A	A											
53366	CRES 14PH-8MO SRH1050 SHEET AIR MELT		A	A											
53381	CRES 14PH-8MO SRH1050 SHEET CVM		A	A											
53364	CRES 14PH-8MO SRH1050 STRIP		A	A											
53361	CRES 14PH-8MO SRH950 SHEET		A	A											
53365	CRES 14PH-8MO SRH950 SHEET AIR MELT		A	A											
53380	CRES 14PH-8MO SRH950 SHEET CVM		A	A											
53362	CRES 14PH-8MO SRH950 STRIP		A	A											
53372	CRES 14PH-8MO STRIP CONDITION A		A	A											
53374	CRES 14PH-8MO STRIP CONDITION C		A	A											
53409	CRES 15PH-5MO FLATS CONDITION A		A	B											
53395	CRES 15PH-5MO H1015 AIR MELTED		A	A											
53394	CRES 15PH-5MO H1025 AIR MELTED		A	A											
10389	CRES 15PH-5MO H1025 BAR SPEC: AMS 5659	MB0160-036	A	A	A	3000	A	A		A		U	X		
53407	CRES 15PH-5MO H1025 BAR AIR MELT		A	A											
53404	CRES 15PH-5MO H1025 BAR CVM		A	A											
53412	CRES 15PH-5MO H1025 ELECTRODE CONSUMABLE BAR		A	A											
50720	CRES 15PH-5MO H1025 FORGING SPEC: MB0160-036		A	A											

MSFC-HDBK-527 REV F 9999942 0004965 5

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50723	CRES 15PH-5MO H1025 FORGING SPEC: AMS 5659		A	A	A		A	A		A		U	X		
10388	CRES 15PH-5MO H1075 BAR SPEC: AMS 5659		A	A	A		A	A		A		U	X		
53413	CRES 15PH-5MO H1075 ELECTRODE CONSUMABLE BAR		A	A											
50726	CRES 15PH-5MO H1075 FORGING SPEC: AMS 5659		A	A	A		A	A		A		U	X		
53396	CRES 15PH-5MO H1100 AIR MELTED		A	A											
53390	CRES 15PH-5MO H1100 BAR		A	A											
53414	CRES 15PH-5MO H1100 ELECTRODE CONSUMABLE BAR		A	A											
53391	CRES 15PH-5MO H1100 FORGING		A	B											
53397	CRES 15PH-5MO H1150 AIR MELTED		A	A											
10387	CRES 15PH-5MO H1150 BAR SPEC: AMS 5659	MB0160-036	A	A	A	3000	A	A		A		U	X		
53408	CRES 15PH-5MO H1150 BAR AIR MELT		A	A											
53405	CRES 15PH-5MO H1150 BAR CVM		A	A											
53415	CRES 15PH-5MO H1150 ELECTRODE CONSUMABLE BAR		A	A											
50727	CRES 15PH-5MO H1150 FORGING SPEC: AMS 5659	MB0160-036	A	A	A		A	A		A		U	X		
10487	CRES 15PH-5MO H1150 TUBE		A	A	A	3300	A	A		A		U	X		
53398	CRES 15PH-5MO H1150M AIR MELTED		A	A											
10078	CRES 15PH-5MO H1150M BAR SPEC: MB0160-036		A	A	A	4500	A	A		A		U	X		
53416	CRES 15PH-5MO H1150M ELECTRODE CONSUMABLE BAR		A	A											
10386	CRES 15PH-5MO H1150M FORGING SPEC: AMS 5659		A	A	A	3000	A	A		A		U	X		
53392	CRES 15PH-5MO H900 AIR MELTED		A	B											
30160	CRES 15PH-5MO H900 BAR SPEC: AMS 5659		A	B	A		A	A		A		U	X		
53406	CRES 15PH-5MO H900 BAR AIR MELT		A	B											

MSFC-HDBK-527 REV F 9999942 0004966 7

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	LH2 RTG	LH2 PRESS	LH2 TEMP
53403	CRES 15PH-5MO H900 BAR CVM		A	B											
53410	CRES 15PH-5MO H900 ELECTRODE CONSUMABLE BAR		A	B											
53387	CRES 15PH-5MO H900 FORGING		A	B											
53400	CRES 15PH-5MO H900 FORGING STOCK		A	B											
53399	CRES 15PH-5MO H900 RINGS FLASH WELDED		A	B	A		A	A		A		U	X		
53402	CRES 15PH-5MO H900 ROUNDS		A	B	A		A	A		A		U	X		
53417	CRES 15PH-5MO H900 WIRE		A	B	A		A	A		A		U	X		
53393	CRES 15PH-5MO H925 AIR MELTED		A	B											
53388	CRES 15PH-5MO H925 BAR		A	B											
53411	CRES 15PH-5MO H925 ELECTRODE CONSUMABLE BAR		A	A											
53389	CRES 15PH-5MO H925 FORGING		A	B											
50728	CRES 15PH-5MO PLATE		A	N	A		A	A		A		U	A		
53401	CRES 15PH-5MO SHAPES CONDITION A		A	N	A		A	A		A		U	A		
10751	CRES 15PH-5MO SHEET		A	N	A		A	A		A		U	A		
50730	CRES 15PH-7MO PLATE SPEC: AMS 5520	MB0160-031	A	N	A		A	A		C		U	X		
10264	CRES 15PH-7MO SHEET SPEC: AMS 5520	MB0160-031	A	N	A	2700	A	A		C		U	X		
50729	CRES 15PH-7MO STRIP SPEC: AMS 5520		A	N	A		A	A		C		U	X		
50227	CRES 15PH-7MO TH1050		A	C	A		A	X		A		U	X		
53104	CRES 16-15-6														
10156	CRES 17PH-4MO 150KSI CASTING INVESTMENT SPEC: AMS 5343		A	B	A	4500	A	A		A		A	X		
10489	CRES 17PH-4MO H1000 CASTING SAND SPEC: AMS 5398		A	B	A	3300	A	A		A		U	X		
10399	CRES 17PH-4MO H1025 BAR SPEC: AMS 5643		A	B	A	3300	A	A		A		U	X		
10378	CRES 17PH-4MO H1025 CASTING INVESTMENT SPEC: AMS 5355		A	B	A		A	A		A		U	X		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0004967 9

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10425	CRES 17PH-4MO H1025 EXTRUSIONS SPEC: MB0160-003		A	B	A	3300	A	A		A		U	X		
10073	CRES 17PH-4MO H1025 FORGING SPEC: MIL-C-24111 CL2		A	B	A		A	A		A		U	X		
50733	CRES 17PH-4MO H1025 PLATE SPEC: AMS 5604		A	B	A		A	A		A		U	X		
50732	CRES 17PH-4MO H1025 RING SPEC: AMS 5643		A	B	A		A	A		A		U	X		
50731	CRES 17PH-4MO H1025 ROD SPEC: AMS 5643	MIL-C-24111 CL2	A	B	A		A	A		A		U	X		
10342	CRES 17PH-4MO H1025 SHEET		A	B	A	3300	A	A		A		U	X		
50734	CRES 17PH-4MO H1025 STRIP		A	B	A		A	A		A		U	X		
10476	CRES 17PH-4MO H1050 BAR SPEC: AMS 5643		A	B	A		A	A		A		U	X		
50735	CRES 17PH-4MO H1050 FORGING SPEC: AMS 5643		A	B	A		A	A		A		U	X		
50736	CRES 17PH-4MO H1050 TUBE SPEC: AMS 5643		A	B	A		A	A		A		U	X		
10693	CRES 17PH-4MO H1075 BAR SPEC: AMS 5622	AMS 5643	A	B	A		A	A		A		U	X		
10430	CRES 17PH-4MO H1075 FORGING SPEC: AMS 5622	AMS 5643	A	B	A	3300	A	A		A		U	X		
52428	CRES 17PH-4MO H1075 RING SPEC: AMS 5622	AMS 5643	A	B	A		A	A		A		U	X		
10688	CRES 17PH-4MO H1075 TUBE SPEC: AMS 5622		A	B	A		A	A		A		U	X		
10471	CRES 17PH-4MO H1100 BAR SPEC: AMS 5643	MIL-C-24111	A	B	A		A	A		A		U	X		
10361	CRES 17PH-4MO H1100 CASTING INVESTMENT SPEC: AMS 5342		A	B	A		A	A		A		U	X		
10074	CRES 17PH-4MO H1150 BAR SPEC: MIL-C-24111 CL3		A	B	A	3300	A	A		A		U	X		
10427	CRES 17PH-4MO H1150 BAR EXTRUDED SPEC: MB0160-003		A	B	A	3300	A	A		A		U	X		

MSFC-HDBK-527 REV F 9999942 0004968 0

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50739	CRES 17PH-4MO H1150 FORGING SPEC: MIL-C-24111 CL3	A	B	A		A	A		A		U	X		
50737	CRES 17PH-4MO H1150 FORGING EXTRUDED SPEC: MB0160-003	A	B	A		A	A		A		U	X		
50738	CRES 17PH-4MO H1150 ROD	A	B	A		A	A		A		U	X		
10435	CRES 17PH-4MO H1150M BAR SPEC: AMS 5643	A	B	A	3300	A	A		A		U	X		
10037	CRES 17PH-4MO H1150M BAR EXTRUDED SPEC: MB0160-018	A	B	A	3300	A	A		A		U	X		
10077	CRES 17PH-4MO H1150M CASTING SPEC: MB0160-013	A	B	A	3300	A	A		A		U	X		
50741	CRES 17PH-4MO H1150M FORGING SPEC: AMS 5643	A	B	A		A	A		A		U	X		
50742	CRES 17PH-4MO H1150M FORGING EXTRUDED SPEC: ASTM A193	A	B	A		A	A		A		U	X		
10075	CRES 17PH-4MO H1150M FORGING EXTRUSION VM SPEC: MB0160-022	A	B	A	3300	A	A		A		U	X		
50743	CRES 17PH-4MO H1150M PLATE SPEC: AMS 5604	A	B	A		A	A		A		U	X		
50740	CRES 17PH-4MO H1150M RING SPEC: AMS 5643	A	B	A		A	A		A		U	X		
10076	CRES 17PH-4MO H1150M SHEET SPEC: AMS5604	A	B	A	3300	A	A		A		U	X		
50744	CRES 17PH-4MO H1150M STRIP SPEC: AMS 5604	A	B	A		A	A		A		U	X		
30159	CRES 17PH-4MO H900 BAR SPEC: AMS 5643	A	B	A		A	A		A		U	C		
50746	CRES 17PH-4MO H900 FORGING SPEC: AMS 5643	A	B	A		A	A		A		U	C		
50747	CRES 17PH-4MO H900 TUBE SPEC: AMS 5643	A	B	A		A	A		A		U	C		
50098	CRES 17PH-4MO H950 BAR SPEC: AMS 5643	A	B	A		A	A		A		U	U		
50748	CRES 17PH-4MO H950 FORGING SPEC: AMS 5643	A	B	A		A	A		A		U	U		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0004969 2

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50749	CRES 17PH-4MO H950 TUBE SPEC: AMS 5643		A	B	A		A	A		A		U	U		
53325	CRES 17PH-4MO PLATE TH1050 SPEC: AMS 5528	MIL-S-25043	A	B	A		A	A		A		U	U		
10409	CRES 17PH-7MO CH900 SHEET SPEC: AMS 5529	MIL-S-25043	A	A	A	3300	A	A		A		X	X		
53338	CRES 17PH-7MO A1750		A	C											
53340	CRES 17PH-7MO BAR CONDITION A SPEC: AMS 5644		A	C											
53335	CRES 17PH-7MO CH900 PLATE SPEC: MIL-S-25043		A	A	A		A	A		A		A	A		
50750	CRES 17PH-7MO CH900 STRIP SPEC: AMS 5529	MIL-S-25043	A	A	A		A	A		A		X	X		
10147	CRES 17PH-7MO CH900 WIRE SPEC: AMS 5678		A	A	A	3300	A	A		A		X	X		
53336	CRES 17PH-7MO CONDITION T		A	C											
53341	CRES 17PH-7MO FORGING CONDITION A SPEC: AMS 5644		A	C											
50752	CRES 17PH-7MO PLATE CONDITION A SPEC: AMS 5528	MIL-S-25043	A	C											
53334	CRES 17PH-7MO PLATE CONDITION C SPEC: MIL-S-25043		A	C											
53339	CRES 17PH-7MO R100		A	C											
50755	CRES 17PH-7MO RH900 PLATE SPEC: AMS 5528	MIL-S-25043	A	C	A		A	A		A		X	X		
30077	CRES 17PH-7MO RH900 SHEET SPEC: AMS 5528	MIL-S-25043	A	C	A	3300	A	A		A		X	X		
50756	CRES 17PH-7MO RH900 STRIP SPEC: AMS 5528	MIL-S-25043	A	C	A		A	A		A		X	X		
53061	CRES 17PH-7MO RH950 200KSI MIN		A	C											
53333	CRES 17PH-7MO RH950 PLATE SPEC: MIL-S-25043		A	C											
53331	CRES 17PH-7MO RH950 SHEET		A	C											

MSFC-HDBK-527 REV F 9999942 0004970 9

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53332	CRES 17PH-7MO RH950 STRIP SPEC: MIL-S-25043		A	C											
30121	CRES 17PH-7MO SHEET CONDITION A SPEC: AMS 5528		A	C	A		A	A		A		X	X		
10451	CRES 17PH-7MO SHEET CONDITION C SPEC: AMS 5678		A	N	A		A	A		A		X	X		
50753	CRES 17PH-7MO STRIP CONDITION A SPEC: AMS 5528	MIL-S-25043	A	C	A		A	A		A		X	X		
50754	CRES 17PH-7MO STRIP CONDITION C SPEC: MIL-S-25043		A	N	A		A	A		A		X	X		
53337	CRES 17PH-7MO TH1050		A	C											
30091	CRES 17PH-7MO TH1050 BAR		A	C	A		A	A		A		X	X		
50757	CRES 17PH-7MO TH1050 FORGING SPEC: AMS 5644		A	C	A		A	A		A		X	X		
53323	CRES 17PH-7MO TH1050 SHEET		A	C											
53324	CRES 17PH-7MO TH1050 STRIP SPEC: AMS 5528	MIL-S-25043	A	C											
53330	CRES 17PH-7MO TH1050 TUBE WELDED SPEC: AMS 5568		A	C	A		A	A		A		X	X		
50758	CRES 17PH-7MO TH1100 PLATE SPEC: MIL-S-25043		A	C	A		A	A		A		X	X		
30020	CRES 17PH-7MO TH1100 SHEET SPEC: MIL-S-25043		A	C	A		A	A		A		X	X		
53329	CRES 17PH-7MO TUBE WELDED CONDITION A SPEC: AMS 5568		A	C											
10516	CRES 17PH-7MO WIRE CONDITION C SPEC: AMS 5678		A	N	A	3300	A	A		A		U	X		
10675	CRES 18-8 (303) WIRE SPEC: AMS 7228		A	A	A		A	A		A		A	A		
53385	CRES 18-8 SHEET AIR MELT BRAZING-CYCLE HEAT TREATED		A	A											
10606	CRES 18-8 SHIM STOCK SPEC: AMS 5500	MIL-S-22499	A	A	A	1000	A	A		A		A	A		
10419	CRES 18-9 WIRE SPRING TEMPER SPEC: AMS 5688		A	A	A	3300	A	A		X		A	A		

MSFC-HDBK-527 REV F ■ 9999942 0004971 0 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
51169	CRES 19-9DL PLATE ANNEALED SPEC: AMS 5526		A	A	A		A	A		A		A	A		
10702	CRES 19-9DL SHEET ANNEALED SPEC: AMS 5526		A	A	A		A	A		A		A	A		
52429	CRES 19-9DL STRIP ANNEALED SPEC: AMS 5526		A	A	A		A	A		A		A	A		
53089	CRES 201 COLD ROLLED		A	A											
52782	CRES 201 SHEET 1/2 HARD		A	A											
52780	CRES 201 SHEET 1/4 HARD		A	A											
52784	CRES 201 SHEET 3/4 HARD		A	A											
52778	CRES 201 SHEET ANNEALED		A	A											
53087	CRES 201 SHEET FULL HARD		A	A											
52783	CRES 201 STRIP 1/2 HARD		A	A											
52781	CRES 201 STRIP 1/4 HARD		A	A											
53086	CRES 201 STRIP 3/4 HARD		A	A											
52779	CRES 201 STRIP ANNEALED		A	A											
53088	CRES 201 STRIP FULL HARD		A	A											
50502	CRES 203EZ BAR ANNEALED SPEC: ASTM A 582	ASTM A484	A	A	A		A	A		X		U	U		
53127	CRES 203EZ BAR COLD FINISHED SPEC: ASTM A582		A	A	A		A	A		X		U	U		
53128	CRES 203EZ BAR FULL HARD SPEC: QQ-S-764		A	A	A		A	A		X		U	U		
53125	CRES 203EZ WIRE ANNEALED SPEC: MIL-W-52263		A	A	A		A	A		X		U	U		
53126	CRES 203EZ WIRE COLD FINISHED SPEC: ASTM A581		A	A	A		A	A		X		U	U		
10104	CRES 21-6-9 BAR ANNEALED SPEC: AMS 5656	MBO160-050	A	A	A		A	A		A		A	A		
50759	CRES 21-6-9 FORGING ANNEALED SPEC: AMS 5656	MBO160-050	A	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F ■ 9999942 0004972 2 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50761	CRES 21-6-9 PLATE ANNEALED SPEC: AMS 5595	MB0160-044	A	A	A		A	A		A		A	A		
50760	CRES 21-6-9 RINGS ANNEALED SPEC: AMS 5656	MB0160-050	A	A	A		A	A		A		A	A		
10103	CRES 21-6-9 SHEET ANNEALED SPEC: AMS 5595	MB0160-044	A	A	A		A	A		A		A	A		
50762	CRES 21-6-9 STRIP ANNEALED SPEC: AMS 5595	MB0160-044	A	A	A		A	A		A		A	A		
10268	CRES 300 SERIES SPEC: AMS 7229 MIL-S-5059 QQ-S-763/766	FED STD 66 MIL-S-6721 QQ-S-766	A	A	A		A	A		A		A	A		
50224	CRES 300 SERIES FASTENERS SPEC: ASTM A493		A	A	A		A	U		U		X	X		
10431	CRES 300 SERIES NON-FREE MACH SPEC: MIL-S-5059 QQ-S-766	QQ-S-763	A	A	A		A	A		A		A	A		
10514	CRES 300 SERIES WIRE SPEC: MIL-W-21632 CLB MIL-W-83420CP-B QQ-S-766	MIL-W-5424CP-B QQ-S-763	A	A	A		A	A		A		A	A		
50766	CRES 301 PLATE 1/4 HARD SPEC: MIL-S-5059		A	A	A		A	A		A		A	A		
10087	CRES 301 PLATE FULL HARD SPEC: MIL-S-5059		A	A	A	1000	A	A		A		A	A		
50515	CRES 301 SHEET 1/4 HARD SPEC: MIL-S-5059		A	A	A		A	A		A		A	A		
10088	CRES 301 SHEET ANNEALED 1/2 HARD 125KSI SPEC: AMS 5517 QQ-S-766	MIL-S-5059	A	A	A	1000	A	A		A		A	A		
50764	CRES 301 SHEET FULL HARD SPEC: MIL-S-5059		A	A	A		A	A		A		A	A		
50767	CRES 301 STRIP 1/4 HARD SPEC: MIL-S-5059		A	A	A		A	A		A		A	A		
50763	CRES 301 STRIP ANNEALED 1/2 HARD 125 KSI SPEC: AMS 5517	QQ-S-766	A	A	A		A	A		A		A	A		

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50765	CRES 301 STRIP FULL HARD SPEC: MIL-S-5059		A	A	A		A	A		A		A	A		
10350	CRES 301/302 SHEET ANNEALED SPEC: MIL-S-5059	QQ-S-766	A	A	A		A	A		A		A	A		
10382	CRES 302 BAR SPEC: QQ-S-763		A	A	A		A	A		A		A	A		
10089	CRES 302 BAR COLD DRAWN 100KSI SPEC: AMS 5636 QQ-S-763	ASTM-A276	A	A	A	1000	A	A		A		A	A		
10423	CRES 302 BAR COLD DRAWN 125KSI SPEC: AMS 5637		A	A	A		A	A		A		A	A		
10601	CRES 302 CASTING INVESTMENT SPEC: AMS 5358		A	A	A	1000	A	A		A		A	A		
50229	CRES 302 CONDITION B SPEC: AMS 5673		A	A	A	3300	A	A		A		X	X		
50770	CRES 302 FORGING SPEC: QQ-S-763		A	A	A		A	A		A		A	A		
50771	CRES 302 PLATE SPEC: AMS 5516	MIL-S-5059	A	A	A		A	A		A		A	A		
10294	CRES 302 PLATE ANNEALED THRU 1/2 HARD SPEC: MIL-S-5059	QQ-S-766	A	A	A	1000	A	A		A		A	A		
50768	CRES 302 ROD SPEC: QQ-S-763		A	A	A		A	A		A		A	A		
50769	CRES 302 SHAPES SPEC: QQ-S-763		A	A	A		A	A		A		A	A		
10262	CRES 302 SHEET SPEC: AMS 5516	MIL-S-5059	A	A	A	1000	A	A		A		A	A		
50366	CRES 302 SHEET 1/2 HARD SPEC: MIL-S-5059	QQ-S-766	A	A	A		A	A		A		A	A		
10148	CRES 302 SPRING CONDITION B WIRE SPEC: ASTM A313	ASTM A580	A	A	A	3300	A	A		A		A	A		
50772	CRES 302 STRIP SPEC: AMS 5516	MIL-S-5059	A	A	A		A	A		A		A	A		
50365	CRES 302 STRIP 1/2 HARD SPEC: MIL-S-5059	QQ-S-766	A	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F ■ 9999942 0004974 6 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10520	CRES 302 WIRE SPEC: AMS 5637 QQ-S-763	AMS 5685	A	A	A		A	A		A		A	A		
10391	CRES 302 WIRE SPRING TEMPER B SPEC: AMS 5688 QQ-S-763	FED STD 66	A	A	A		A	A		A		A	A		
10349	CRES 302/304 1/4 HARD SPEC: MIL-S-5059		A	A	A		A	A		A		A	A		
10334	CRES 302/304 FASTENER ONLY SPEC: QQ-S-763		A	A	A		A	A		A		A	A		
10315	CRES 302/304/316 FASTENRS ONLY SPEC: MIL-S-5059 MIL-S-7720	MIL-S-6721 QQ-S-763	A	A	A		A	A		A		A	A		
30080	CRES 303 BAR FREE MACHINE SPEC: AMS 5640 FED STD 66 QQ-S-763	ASTM A 582 MIL-S-7720	A	A	A		A	A		A		A	A		
50773	CRES 303 FORGING FREE MACHINE SPEC: AMS 5640		A	A	A		A	A		A		A	A		
50774	CRES 303 WIRE SPEC: MIL-I-8846	QQ-S-763	A	A	A		A	A		A		A	A		
10506	CRES 303/304 BAR SPEC: ASTM A582 QQ-S-763	MIL-I-8846	A	A	A		A	A		A		A	A		
10512	CRES 303/305 BAR SPEC: ASTM A582	FED STD 66	A	A	A		A	A		A		A	A		
52756	CRES 303SE BAR CAST SPEC: ASTM A296		A	A											
52747	CRES 303SE BAR COLD FINISHED SPEC: AMS 5641		A	A											
52753	CRES 303SE BAR HI-TENSION SPEC: AMS 5738		A	A											
52748	CRES 303SE BAR SOLUTION TREATED SPEC: AMS 5641		A	A											
52750	CRES 303SE BOLTING MATERIAL SOLUTION TREATED SPEC: ASTM A320		A	A											

MSFC-HDBK-527 REV F 9999942 0004975 8

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52752	CRES 303SE CASTING SOLUTION TREATED SPEC: ASTM A296		A	A											
52751	CRES 303SE FORGING SOLUTION TREATED SPEC: AMS 5641		A	A											
52755	CRES 303SE WIRE FULL HARD		A	A											
52754	CRES 303SE WIRE SOFT		A	A											
52749	CRES 303SE WIRE SOLUTION TREATED		A	A											
10432	CRES 304 1/4 HARD FOIL COLD ROLL SPEC: AMS 5501		A	A	A	3300	A	A		A		A	A		
10351	CRES 304 BAR ANNEALED SPEC: AMS 5639 MB0160-046 QQ-S-763	ASTM A 276 MIL-S-23195	A	A	A		A	A		A		A	A		
10091	CRES 304 BAR CONDITION B SPEC: QQ-S-763		A	A	A	3300	A	A		A		A	A		
10674	CRES 304 CASTING INVESTMENT ANNEALED SPEC: ASTM A 296 GR 8		A	A	A	3300	A	A		A		A	A		
50721	CRES 304 FORGING (CRES 30304) SPEC: AMS 5639		A	A	A		A	A		A		U	X		
50775	CRES 304 FORGING ANNEALED SPEC: AMS 5639 MB0160-046 QQ-S-763	ASTM A 276 MIL-S-23195	A	A	A		A	A		A		A	A		
50780	CRES 304 FORGING CONDITION B SPEC: QQ-S-763		A	A	A		A	A		A		A	A		
50085	CRES 304 PLATE SPEC: ASTM A-240		A	A	A		A	A		A		U	U		
10090	CRES 304 PLATE ANNEALED SPEC: AMS 5513	QQ-S-766	A	A	A	3300	A	A		A		A	A		
10375	CRES 304 PLATE ANNEALED THRU 1/2 HARD SPEC: MIL-S-5059		A	A	A	3300	A	A		A		A	A		
50782	CRES 304 PLATE HARD SPEC: MIL-S-5059		A	A	A		A	A		A		A	A		
50779	CRES 304 SHAPE CONDITION B SPEC: QQ-S-763		A	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004976 T

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	LH2 RTG	LH2 PRESS	LH2 TEMP
50784	CRES 304 SHEET SPEC: ASTM A-240		A	A	A		A	A		A		U	U		
50777	CRES 304 SHEET ANNEALED SPEC: AMS 5513	QQ-S-766	A	A	A		A	A		A		A	A		
50367	CRES 304 SHEET ANNEALED THRU 1/2 HARD SPEC: QQ-S-766		A	A	A		A	A		A		A	A		
10263	CRES 304 SHEET HARD SPEC: MIL-S-5059		A	A	A	3300	A	A		A		A	A		
10645	CRES 304 SPRING WIRE FULL HARD SPEC: ASTM A313	ASTM A580	A	A	A		A	A		A		A	A		
50785	CRES 304 STRIP SPEC: ASTM A-240		A	A	A		A	A		A		U	U		
50778	CRES 304 STRIP ANNEALED SPEC: AMS 5513	QQ-S-766	A	A	A		A	A		A		A	A		
50783	CRES 304 STRIP HARD SPEC: MIL-S-5059		A	A	A		A	A		A		A	A		
10436	CRES 304 TUBE 1/8 HARD SPEC: MIL-T-6845		A	A	A	3300	A	A		A		A	A		
50776	CRES 304 TUBE ANNEALED SPEC: AMS 5639		A	A	A		A	A		A		A	A		
10413	CRES 304 TUBE/PTFE ANNEALED SPEC: AMS 5560 ASTM-A-312 MIL-T-8506	ASTM-A-269 MIL-T-8504	A	A	A	3300	A	A		A		A	A		
10220	CRES 304 WIRE ANNEALED SPEC: AMS 5697	QQ-W-423	A	A	A	3300	A	A		A		A	A		
50781	CRES 304 WIRE CONDITION B SPEC: QQ-S-763		A	A	A		A	A		A		A	A		
50093	CRES 304 WIRE FABRIC SPEC: RR-W-360		A	A	U		U	A		A		U	U		
10233	CRES 304L BAR ANNEALED SPEC: MBO160-037		A	A	A	3300	A	A		A		A	A		
10155	CRES 304L CASTING INVESTMENT		A	A	A	3300	A	A		A		A	A		
50786	CRES 304L FORGING SPEC: AMS 5647	QQ-S-763	A	A	A		A	A		A		U	U		

MSFC-HDBK-527 REV F 9999942 0004977 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	LH2 RTG	LH2 PRESS	LH2 TEMP
50788	CRES 304L FORGING ANNEALED VM SPEC: MB0160-037		A	A	A		A	A		A		A	A		
50790	CRES 304L PLATE ANNEALED SPEC: AMS 5511	MIL-S-4043	A	A	A		A	A		A		A	A		
10306	CRES 304L ROD ANNEALED SPEC: AMS 5647	QQ-S-763	A	A	A	3300	A	A		A		A	A		
50789	CRES 304L ROD ANNEALED VM SPEC: MB0160-037		A	A	A		A	A		A		A	A		
10092	CRES 304L SHEET ANNEALED SPEC: AMS 5511 QQ-S-766	MIL-S-4043	A	A	A	3300	A	A		A		A	A		
52769	CRES 304L SHEET COLD ROLLED		A	A	A		A	A		A		A	A		
50791	CRES 304L STRIP ANNEALED SPEC: AMS 5511	MIL-S-4043	A	A	A		A	A		A		A	A		
50787	CRES 304L TUBE SPEC: AMS 5647	QQ-S-763	A	A	A		A	A		A		A	A		
10093	CRES 304L TUBE CONDITION A & B SPEC: MB0160-007		A	A	A	3300	A	A		A		A	A		
50071	CRES 304L WIRE SPEC: QQ-W-423		A	A	A		A	A		A		U	U		
10318	CRES 304L WIRE SCREEN SPEC: MB0160-016	QQ-S-763	A	A	A		A	A		A		A	A		
10336	CRES 305 BAR ANNEALED SPEC: QQ-S-763		A	A	A		A	A		A		A	A		
50793	CRES 305 PLATE SPEC: AMS 5514		A	A	A		A	A		A		A	A		
10475	CRES 305 SHEET SPEC: AMS 5514		A	A	A		A	A		A		A	A		
50794	CRES 305 STRIP SPEC: AMS 5514		A	A	A		A	A		A		A	A		
10622	CRES 305 WIRE SPEC: QQ-W-423		A	A	A		A	A		A		A	A		
10633	CRES 310 BAR ANNEALED SPEC: QQ-S-763		A	A	A	1000	A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004978 3

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	MDZE RTG	MDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50798	CRES 310 FORGING	A	A	A		A	A		A		A	A		
50795	CRES 310 PLATE ANNEALED SPEC: QQ-S-766	A	A	A		A	A		A		A	A		
50797	CRES 310 SHAPE	A	A	A		A	A		A		A	A		
10094	CRES 310 SHEET ANNEALED SPEC: QQ-S-766	A	A	A	1000	A	A		A		A	A		
50796	CRES 310 STRIP ANNEALED SPEC: QQ-S-766	A	A	A		A	A		A		A	A		
52723	CRES 314 BAR ANNEALED SPEC: AMS 5652	A	A											
52732	CRES 314 BAR COLD FINISHED SPEC: AMS 5652	A	A											
52733	CRES 314 BAR HOT FINISHED SPEC: AMS 5652	A	A											
52734	CRES 314 FORGING SPEC: AMS 5652	A	A											
52724	CRES 314 PLATE ANNEALED SPEC: AMS 5522	A	A											
52726	CRES 314 PLATE HOT ROLLED SPEC: AMS 5522	A	A											
52725	CRES 314 SHEET ANNEALED SPEC: AMS 5522	A	A											
52727	CRES 314 SHEET COLD ROLLED SPEC: AMS 5522	A	A											
52728	CRES 314 STRIP ANNEALED SPEC: AMS 5522	A	A											
52729	CRES 314 STRIP COLD ROLLED SPEC: AMS 5522	A	A											
52730	CRES 314 TUBE ANNEALED MECHANICAL SPEC: AMS 5652	A	A											
52731	CRES 314 TUBE COLD FINISHED MECHANICAL SPEC: AMS 5652	A	A											
52721	CRES 314 WIRE ANNEALED SPEC: AMS 5652	A	A											

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0004979 5

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52722	CRES 314 WIRE COLD FINISHED SPEC: AMS 5652		A	A											
52735	CRES 316 ANNEALED		A	A	A		A	A		A		A	A		
10370	CRES 316 BAR CONDITION A SPEC: AMS 5524 ASTM A276 QQ-S-763	ASTM A182 ASTM A479	A	A	A		A	A		A		A	A		
50059	CRES 316 BAR CONDITION A SPEC: QQ-S-763		A	A	A		A	A		A		U	U		
52741	CRES 316 CASTING SPEC: AMS 5360		A	A	A		A	A		A		A	A		
10159	CRES 316 CASTING INVESTMENT ANNEALED SPEC: AMS 5360	ASTM-A351	A	A	A		A	A		A		A	A		
52740	CRES 316 FORGING ANNEALED SPEC: AMS 5649		A	A	A		A	A		A		A	A		
52742	CRES 316 MATERIAL BOLTING SPEC: ASTM A193		A	A	A		A	A		A		A	A		
50799	CRES 316 PLATE ANNEALED SPEC: MIL-S-5059	QQ-S-766	A	A	A		A	A		A		A	A		
10095	CRES 316 SHEET ANNEALED		A	A	A	1000	A	A		A		A	A		
52739	CRES 316 SPRING TEMPER		A	A	A		A	A		A		A	A		
10296	CRES 316 SPRING WIRE CONDITION B SPEC: ASTM A313	ASTM A580	A	A	A	1000	A	A		A		A	A		
50800	CRES 316 STRIP ANNEALED SPEC: MIL-S-5059	QQ-S-766	A	A	A		A	A		A		A	A		
52736	CRES 316 TUBE ANNEALED SPEC: AMS 5573		A	A	A		A	A		A		A	A		
10474	CRES 316 TUBE SEAMLESS SPEC: AMS 5573	ASTM A 312	A	A	A	1000	A	A		A	0160	A	A		
52737	CRES 316 WIRE ANNEALED SPEC: AMS 5690		A	A	A		A	A		A		A	A		
10219	CRES 316 WIRE CONDITION A & B SPEC: QQ-W-423	RR-W-360	A	A	A	1000	A	A		A		A	A		
52738	CRES 316 WIRE SOFT SPEC: AMS 5690		A	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004980 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDXE RTG	HDXE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10083	CRES 316L BAR ANNEALED SPEC: QQ-S-763		A	A	A	1000	A	A		A		A	A		
50512	CRES 316L CASTING INVESTMENT ANNEALED		A	A	A	1000	A	A		A		A	A		
50804	CRES 316L FORGING ANNEALED SPEC: QQ-S-763		A	A	A		A	A		A		A	A		
50801	CRES 316L PLATE ANNEALED SPEC: AMS 5507	QQ-S-766	A	A	A		A	A		A		A	A		
50803	CRES 316L SHAPE ANNEALED SPEC: QQ-S-763		A	A	A		A	A		A		A	A		
10096	CRES 316L SHEET ANNEALED SPEC: AMS 5507	QQ-S-766	A	A	A	1000	A	A		A		A	A		
50802	CRES 316L STRIP ANNEALED SPEC: AMS 5507	QQ-S-766	A	A	A		A	A		A		A	A		
50805	CRES 316L WIRE ANNEALED SPEC: QQ-S-763		A	A	A		A	A		A		A	A		
50792	CRES 316L WIRE SCREEN SPEC: MB0160-016		A	A	A		A	A		A		A	A		
52712	CRES 317 ANNEALED SPEC: QQ-S-766		A	A	A		A	A		A		A	A		
50147	CRES 317 CONDITION 1/4 HARD		A	A	A		A	A		A		U	U		
50203	CRES 320 FILLER MATERIAL SPEC: RB0170-236		A	N	U		U	U		U		U	U		
10098	CRES 321 BAR ANNEALED SPEC: AMS 5645	QQ-S-763	A	A	A	1000	A	A		A		A	A		
52720	CRES 321 BAR COLD FINISHED SPEC: AMS 5645		A	A	A		A	A		A		A	A		
52717	CRES 321 FLAT EXTRUDED ANNEALED		A	A	A		A	A		A		A	A		
10380	CRES 321 FOIL SPEC: MB0160-045	MIL-S-6721	A	A	A		A	A		A		A	A		
50806	CRES 321 FORGING ANNEALED SPEC: AMS 5645	QQ-S-763	A	A	A		A	A		A		A	A		
52718	CRES 321 JOINTS BRAZED ANNEALED		A	A	A		A	A		A		A	A		
50808	CRES 321 PLATE ANNEALED SPEC: AMS 5510 QQ-S-766	MIL-S-6721	A	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F ■ 9999942 0004981 3 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10097	CRES 321 SHEET ANNEALED SPEC: AMS 5510	MIL-S-6721	A	A	A	1000	A	A		A		A	A		
50809	CRES 321 STRIP ANNEALED SPEC: AMS 5510 QQ-S-766	MIL-S-6721	A	A	A		A	A		A		A	A		
50807	CRES 321 TUBE ANNEALED SPEC: QQ-S-763		A	A	A		A	A		A		A	A		
10101	CRES 321 TUBE ANNEALED SEAMLESS SPEC: AMS 5557 AMS 5576 MIL-T-8606	AMS 5570 ASTM A 312 MIL-T-8808	A	A	A	1000	A	A		A		A	A		
52719	CRES 321 WIRE ANNEALED SPEC: AMS 5689		A	A	A		A	A		A		A	A		
10102	CRES 341 TUBE ANNEALED SEAMLESS SPEC: AMS 5556 MIL-T-8808 TY1	AMS 5571	A	A	A	4500	A	A		A		A	A		
52773	CRES 347 BAR ANNEALED SPEC: AMS 5646	QQ-S-763	A	A	A		A	A		A		A	A		
52774	CRES 347 CASTING ANNEALED SPEC: AMS 5363	MIL-S-867	A	A	A		A	A		A		A	A		
10157	CRES 347 CASTING INVESTMENT ANNEALED SPEC: AMS 5362		A	A	A	4500	A	A		A		A	A		
52775	CRES 347 FORGING ANNEALED SPEC: ASTM A314	ASTM A473	A	A	A		A	A		A		A	A		
52776	CRES 347 HOT EXTRUDED														
50810	CRES 347 PLATE ANNEALED SPEC: AMS 5512 QQ-S-766	MIL-S-6721	A	A	A		A	A		A		A	A		
10671	CRES 347 RIVET CONDITION A SPEC: AMS 7229		A	A	A		A	A		A		A	A		
10099	CRES 347 SHEET ANNEALED SPEC: AMS 5512 QQ-S-766	MIL-S-6721	A	A	A	4500	A	A		A		A	A		
50811	CRES 347 STRIP ANNEALED SPEC: AMS 5512		A	A	A		A	A		A		A	A		
10227	CRES 347 TUBE ANNEALED SPEC: AMS 5556 MIL-T-8808	MIL-T-8606	A	A	A	4500	A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004982 5

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10455	CRES 347 WIRE CONDITION A & B SPEC: QQ-W-423		A	A	A		A	A		A		A	A		
50225	CRES 400 SERIES FASTENERS SPEC: ASTM A493		A	B	A		A	U		U		X	X		
53234	CRES 403 BAR ANNEALED SPEC: ASTM A276		A	A											
53236	CRES 403 BAR COLD DRAWN SPEC: ASTM A276		A	A											
53235	CRES 403 BAR TEMPERED SPEC: ASTM A276	ASTM A314	A	A											
53240	CRES 403 BILLET SPEC: ASTM A276	ASTM A314	A	A											
53233	CRES 403 PLATE ANNEALED		A	A											
53231	CRES 403 SHEET ANNEALED		A	A											
53232	CRES 403 STRIP		A	A											
53237	CRES 403 WIRE ANNEALED		A	A											
53238	CRES 403 WIRE COLD DRAWN		A	A											
53239	CRES 403 WIRE TEMPERED		A	A											
30114	CRES 410 BAR ANNEALED SPEC: FED-STD-66	QQ-S-763	B	B	A		A	X		X		X	X		
50814	CRES 410 PLATE ANNEALED SPEC: AMS 5504		B	B	A		A	X		X		X	X		
50129	CRES 410 SHEET ANNEALED		B	B	A		A	X		X		X	X		
50815	CRES 410 STRIP		B	B	A		A	X		X		X	X		
53302	CRES 410CB BAR ANNEALED SPEC: AMS 5609		B	B											
53301	CRES 410CB BAR QUENCHED & TEMPERED SPEC: AMS 5609		B	B											
53303	CRES 410CB FORGING QUENCHED & TEMPERED SPEC: AMS 5609		B	B											
53305	CRES 410CB FORGING STOCK QUENCHED & TEMPERED SPEC: AMS 5609		B	B											

MSFC-HDBK-527 REV F 9999942 0004983 7

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53304	CRES 410CB TUBING MECHANICAL QUENCHED & TEMPERED SPEC: AMS 5609		B	B											
30075	CRES 416 BAR ANNEALED SPEC: AMS 5610	ASTM A582	B	B	A	1000	A	X		X		X	X		
50065	CRES 416 BAR COLD FINISHED SPEC: QQ-S-763		B	B	U		U	C		C		U	U		
50066	CRES 416 BAR QUENCHED & TEMPERED SPEC: QQ-S-763		B	B	A		A	X		X		X	X		
53226	CRES 416 CASTINGS PRECISION INVESTMENT QUENCHED & TEMPERED SPEC: AMS 5349		B	B											
53230	CRES 416 FORGING ANNEALED SPEC: AMS 5610		B	B	A		A	X		X		X	X		
53227	CRES 416 WIRE ANNEALED		B	B	A		A	X		X		X	X		
53228	CRES 416 WIRE COLD FINISHED		B	B	U		U	C		C		U	U		
53229	CRES 416 WIRE QUENCHED & TEMPERED		B	B											
50205	CRES 419		U	B	U		U	U		U		U	U		
50503	CRES 420 SPEC: AMS 5506		B	B	A		A	X		C		X	X		
30136	CRES 420 BAR SPEC: QQ-S-763		B	B	U		U	X		X		X	X		
52437	CRES 420 PLATE SPEC: AMS 5506		B	B	U		U	X		X		X	X		
52438	CRES 420 SHEET SPEC: AMS 5506		B	B	U		U	X		X		X	X		
52439	CRES 420 STRIP SPEC: AMS 5506		B	B	U		U	X		X		X	X		
30066	CRES 430 BAR ANNEALED SPEC: AMS 5627	QQ-S-763	B	A	A	1000	A	X		X		X	X		
52441	CRES 430 FORGING ANNEALED SPEC: AMS 5627		B	A	A	1000	A	X		X		X	X		
52440	CRES 430 SHAPES ANNEALED SPEC: AMS 5627	QQ-S-763	B	A	A	1000	A	X		X		X	X		
50121	CRES 430 WIRE														

MSFC-HDBK-527 REV F ■ 9999942 0004984 9 ■

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52442	CRES 430 WIRE ANNEALED SPEC: AMS 5627	B	A	A	1000	A	X		X		X	X		
30120	CRES 431 BAR ANNEALED SPEC: QQ-S-763	B	A	A		A	X		X		X	X		
53268	CRES 431 BAR COLD FINISHED SPEC: AMS 5628	B	B											
53271	CRES 431 BAR HOT FINISHED SPEC: AMS 5628	B	B											
50817	CRES 431 BAR QUENCHED AND TEMPERED	B	B											
53270	CRES 431 BILLET QUENCHED & TEMPERED	B	B											
53264	CRES 431 CASTING ANNEALED SPEC: AMS 5372	B	B											
53276	CRES 431 CASTING AS CAST SPEC: AMS 5372	B	B											
53272	CRES 431 CASTING INVESTMENT HOT FINISHED SPEC: AMS 5353	B	B											
53274	CRES 431 CASTING INVESTMENT NORMALIZED & TEMPERED SPEC: AMS 5353	B	B											
53273	CRES 431 CASTING NORMALIZED & TEMPERED SPEC: AMS 5372	B	B											
53266	CRES 431 CASTING PRECISION QUENCHED & TEMPERED	B	B											
53265	CRES 431 CASTING QUENCHED & TEMPERED SPEC: AMS 5372	B	B											
50816	CRES 431 FORGING PANCAKE QUENCHED AND TEMPERED SPEC: QQ-S-763	B	B											
53269	CRES 431 TUBING MECHANICAL COLD FINISHED SPEC: AMS 5628	B	B											
53267	CRES 431 WIRE COLD FINISHED SPEC: AMS 5628	B	B											
53275	CRES 431 WIRE SOFT SPEC: AMS 5628	B	B											
50819	CRES 440 BAR SPEC: COMMERCIAL GR	B	C											

MSFC-HDBK-527 REV F ■ 9999942 0004985 0 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50818	CRES 440 PLATE SPEC: COMMERICAL GR		B	C	A		A	U		U		X	X		
50820	CRES 440 ROD SPEC: COMMERCIAL GR		B	C											
50097	CRES 440 SHEET SPEC: COMMERCIAL GR		B	C	A		A	U		U		X	X		
30002	CRES 440A BAR ANNEALED SPEC: AMS 7445	QQ-S-763	B	A	A	1500	A	A		A		X	X		
53137	CRES 440A BAR COLD FINISHED SPEC: AMS 5631		B	A											
50064	CRES 440A BAR QUENCHED AND TEMPERED SPEC: QQ-S-763		B	A	A		A	X		X		X	X		
53141	CRES 440A CASTINGS INVESTMENT ANNEALED		B	A											
53142	CRES 440A CASTINGS INVESTMENT QUENCHED & TEMPERED		B	A											
53140	CRES 440A FORGING ANNEALED SPEC: AMS 5631		B	A											
53138	CRES 440A WIRE ANNEALED		B	A											
53139	CRES 440A WIRE SOFT		B	A											
50821	CRES 440B BAR ANNEALED SPEC: AMS 7445	QQ-S-763	B	A											
53132	CRES 440B BAR COLD FINISHED		B	A											
50823	CRES 440B BAR QUENCHED & TEMPERED SPEC: QQ-S-763		B	A											
53135	CRES 440B CASTINGS INVESTMENT ANNEALED		B	A											
53136	CRES 440B CASTINGS INVESTMENT QUENCHED & TEMPERED		B	A											
53133	CRES 440B WIRE ANNEALED		B	A											
53134	CRES 440B WIRE SOFT		B	A											
50822	CRES 440C BAR ANNEALED SPEC: AMS 7445	QQ-S-763	B	C											
30008	CRES 440C BAR COLD FINISHED SPEC: AMS 5630C		B	C	A	1500	A	X		X		X	X		

MSFC-HDBK-527 REV F 9999942 0004986 2

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	NDMH RTG	NDMH TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10106	CRES 440C BAR QUENCHED AND TEMPERED SPEC: MB0160-021	B	C	A	1500	A	A		A		X	X		
53131	CRES 440C CASTINGS INVESTMENT ANNEALED SPEC: AMS 5352A	B	C											
50824	CRES 440C CASTINGS INVESTMENT QUENCHED & TEMPERED SPEC: QQ-S-763	B	C											
50825	CRES 440C FORGING ANNEALED SPEC: AMS 5630C	B	C											
53129	CRES 440C WIRE ANNEALED	B	C											
53130	CRES 440C WIRE SOFT	B	C											
53111	CRES 440F BAR ANNEALED SPEC: AMS 5632C	B	A											
53112	CRES 440F CASTINGS INVESTMENT ANNEALED	B	A											
53113	CRES 440F CASTINGS INVESTMENT QUENCHED AND TEMPERED	B	A											
53110	CRES 440F WIRE COLD FINISHED SPEC: AMS 5632C	B	A											
30094	CRES 446 BAR SPEC: QQ-S-763	B	A	U		A	A		A		X	X		
52445	CRES 446 FORGING	B	A	U		A	A		A		X	X		
30093	CRES 446 PLATE	B	A	U		A	A		A		U	U		
52444	CRES 446 SHAPES	B	A	U		A	A		A		X	X		
52446	CRES 446 SHEET	B	A	U		A	A		A		U	U		
52447	CRES 446 STRIP	B	A	U		A	A		A		U	U		
52443	CRES 446 WIRE	B	A	U		A	A		A		X	X		
50069	CRES A286 95KSI YIELD SPEC: MSFC-SPEC-145	A	A	A		A	A		A		A	A		
53423	CRES A286 AGED	A	A	A		A	A		A		A	A		
10456	CRES A286 BAR 130-140KSI UTS SPEC: AMS 5732	A	A	A		A	A		A		A	A		
10518	CRES A286 BAR 130-190KSI SPEC: AMS 5659 AMS-5732	A	A	A		A	A		A		A	X		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0004987 4

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10011	CRES A286 BAR 140 KSI SPEC: AMS 5731		A	A	A	2000	A	A		A		A	A		
50084	CRES A286 BAR 180KSI SPEC: AMS 5731		A	A	A		A	A		A		A	A		
53427	CRES A286 BAR >140KSI UTS SPEC: AMS 5732B		A	A	A		A	A		A		A	A		
53425	CRES A286 BAR ANNEALED SPEC: AMS 5734A		A	A	A		A	A		A		A	A		
53426	CRES A286 BAR QUENCHED SPEC: AMS 5732B		A	A	A		A	A		A		A	A		
53424	CRES A286 COLD REDUCED		A	A	A		A	A		A		A	A		
10267	CRES A286 FASTENER MATERIAL SH SPEC: AMS 5525 AMS 5731 AMS 5734 AMS 5735 AMS 5736 AMS 5737		A	A	A	1000	A	A		A		A	A		
50140	CRES A286 FASTENERS 160KSI MIN UTS SPEC: AMS 7479		A	A	A		A	A		A		A	A		
10125	CRES A286 FORGING 140KSI SPEC: AMS 5734		A	A	A	1000	A	A		A		A	A		
50709	CRES A286 PLATE 140KSI UTS SPEC: AMS 5525		A	A	A		A	A		A		A	A		
53420	CRES A286 PLATE ANNEALED SPEC: AMS 5525B		A	A	A		A	A		A		A	A		
53430	CRES A286 RINGS 130-140KSI, UTS SPEC: AMS 5731 AMS 5732B		A	A	A		A	A		A		A	A		
10392	CRES A286 SHAPE SPEC: AMS 5732		A	A	A	1000	A	A		A		A	A		
10124	CRES A286 SHEET 140KSI UTS SPEC: AMS 5525		A	A	A	1000	A	A		A		A	A		
53429	CRES A286 SHEET >140KSI, UTS SPEC: AMS 5525B		A	A	A		A	A		A		A	A		
53418	CRES A286 SHEET ANNEALED SPEC: AMS 5525B		A	A	A		A	A		A		A	A		
50717	CRES A286 SHEET W/AL 800		A	A	A		A	A		A		A	A		

MSFC-HDBK-527 REV F 9999942 0004988 6

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZK RTG	HDZK TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53428	CRES A286 STOCK >140KSI, UTS		A	A	A		A	A		A		A	A		
53421	CRES A286 STRIP 140KSI UTS SPEC: AMS 5525B		A	A	A		A	A		A		A	A		
53419	CRES A286 STRIP ANNEALED SPEC: AMS 5525B		A	A	A		A	A		A		A	A		
53422	CRES A286 TUBE 130-140KSI UTS SPEC: AMS 5731	AMS 5732B	A	A	A		A	A		A		A	A		
50708	CRES A286 TUBE 140KSI SPEC: AMS 5731		A	A	A		A	A		A		A	A		
50706	CRES A286 WIRE		A	A	A		A	A		A		A	A		
53107	CRES AFC-77 ANNEALED		A	U											
53105	CRES AFC-77 BAR QUENCHED AND TEMPERED		A	U											
53106	CRES AFC-77 SHEET		A	U											
53293	CRES AM-350 BAR DA SPEC: AMS 5745		A	A											
53281	CRES AM-350 CONDITION H		A	A											
53299	CRES AM-350 ELECTRODES WELDING SPEC: AMS 5775		A	A											
53282	CRES AM-350 SCT ALL		A	A											
53290	CRES AM-350 SCT1000 BAR SPEC: AMS 5745		A	A	A		A	A		A		A	A		
53291	CRES AM-350 SCT1000 FORGING SPEC: AMS 5745		A	A	A		A	A		A		A	A		
10084	CRES AM-350 SCT1000 TUBE SPEC: AMS 5554		A	A	A		A	A		A		A	U		
53292	CRES AM-350 SCT850 BAR SPEC: AMS 5745		A	A											
53283	CRES AM-350 SCT850 SHEET SPEC: AMS 5548		A	B											
53284	CRES AM-350 SCT850 STRIP SPEC: AMS 5548		A	B											
53296	CRES AM-350 SHEET AS WELDED		A	A											

MSFC-HDBK-527 REV F 9999942 0004989 8

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53298	CRES AM-350 SHEET BRAZED AND HEAT TREATED SPEC: AMS 5546		A	A											
53285	CRES AM-350 SHEET COLD ROLLED & TEMPERED SPEC: AMS 5546		A	A											
53286	CRES AM-350 SHEET CONDITION H SPEC: AMS 5546		A	A											
53294	CRES AM-350 SHEET CONDITION L SPEC: AMS 5546		A	A											
53295	CRES AM-350 SHEET DA SPEC: AMS 5546		A	A											
53297	CRES AM-350 SHEET WELD AND HEAT TREATED		A	A											
53287	CRES AM-350 STRIP COLD ROLLED & TEMPERED SPEC: AMS 5546		A	A											
53288	CRES AM-350 STRIP CONDITION H SPEC: AMS 5546		A	A											
53289	CRES AM-350 TUBE DA SPEC: AMS 5554		A	A											
53300	CRES AM-350 WIRE WELDING SPEC: AMS 5774		A	A											
53114	CRES AM-363 SHEET ANNEALED		A	A											
53115	CRES AM-363 SHEET HOT ROLLED		A	A											
52704	CRES CK-20 CASTING ANNEALED		A	A											
52705	CRES CK-20 CASTING ANNEALED HIGH TEMP SERVICE SPEC: ASTM A351		A	A											
52706	CRES CK-20 PIPE ANNEALED CENTRIFUGAL CAST SPEC: ASTM A451		A	A											
53202	CRES CUSTOM 450 BAR ANNEALED SPEC: AMS 5763	AMS 5773	A	A											
53206	CRES CUSTOM 450 H1000 BAR SPEC: AMS 5763	AMS 5773	A	A											
53204	CRES CUSTOM 450 H1050 BAR SPEC: AMS 5763	AMS 5773	A	A											
53207	CRES CUSTOM 450 H1100 BAR SPEC: AMS 5763	AMS 5773	A	A											

MSFC-HDBK-527 REV F 9999942 0004990 4

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	NDMH RTG	NDMH TEMP	LOH2 RTG	NIH2 RTG	NIH2 PRESS	NIH2 TEMP
53208	CRES CUSTOM 450 H1150 BAR SPEC: AMS 5763	AMS 5773	A	A											
53203	CRES CUSTOM 450 H900 BAR SPEC: AMS 5763	AMS 5773	A	A											
53205	CRES CUSTOM 450 H950 BAR SPEC: AMS 5763	AMS 5773	A	A											
10694	CRES CUSTOM 455 H1000 SPEC: AMS 5617 QQ-S-766	AMS 7245	A	A	A		A	U		U		U	U		
50138	CRES CUSTOM 455 H1050		A	A	A		A	U		U		U	U		
30126	CRES CUSTOM 455 H950 SPEC: AMS 5617		A	C	U		U	U		U		U	U		
10718	CRES DISCALOY SPEC: AMS 5733		A	A	A		A	A		A		A	A		
50710	CRES E-BRITE Z6-1 SHAPE SPEC: ASTM A-479 XM-27		A	A											
50711	CRES E-BRITE Z6-1 WIRE SPEC: ASTM A-479 XM-27		A	A											
53311	CRES GREEK ASCOLOY BAR ANNEALED SPEC: AMS 5616		B	U	U		U	U		U		U	U		
30090	CRES GREEK ASCOLOY BAR QUENCHED & TEMPERED SPEC: AMS 5616		B	U	U		U	U		U		U	U		
53312	CRES GREEK ASCOLOY BILLET ANNEALED		B	U	U		U	U		U		U	U		
53310	CRES GREEK ASCOLOY CASTINGS INVESTMENT QUENCHED & TEMPERED SPEC: AMS 5354		B	U	U		U	U		U		U	U		
53313	CRES GREEK ASCOLOY FLAT EXTRUDED ANNEALED		B	U	U		U	U		U		U	U		
53314	CRES GREEK ASCOLOY FLAT EXTRUDED QUENCHED & TEMPERED		B	U	U		U	U		U		U	U		
50686	CRES GREEK ASCOLOY FORGING QUENCHED AND TEMPERED SPEC: AMS 5616		B	U	U		U	U		U		U	U		
53308	CRES GREEK ASCOLOY PLATE ANNEALED SPEC: AMS 5508		B	U	U		U	U		U		U	U		
53319	CRES GREEK ASCOLOY PLATE QUENCHED & TEMPERED SPEC: AMS 5508		B	U	U		U	U		U		U	U		

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53322	CRES GREEK ASCOLOY QUENCHED & TEMPERED	B	U	U		U	U		U		U	U		
53315	CRES GREEK ASCOLOY RINGS WELDED ANNEALED	B	U	U		U	U		U		U	U		
53306	CRES GREEK ASCOLOY SHEET ANNEALED SPEC: AMS 5508	B	U	U		U	U		U		U	U		
53317	CRES GREEK ASCOLOY SHEET QUENCHED & TEMPERED SPEC: AMS 5508	B	U	U		U	U		U		U	U		
53307	CRES GREEK ASCOLOY STRIP ANNEALED SPEC: AMS 5508	B	U	U		U	U		U		U	U		
53318	CRES GREEK ASCOLOY STRIP QUENCHED & TEMPERED SPEC: AMS 5508	B	U	U		U	U		U		U	U		
53316	CRES GREEK ASCOLOY TUBE COLD FINISHED SPEC: AMS 5616	B	U	U		U	U		U		U	U		
50687	CRES GREEK ASCOLOY TUBE QUENCHED & TEMPERED SPEC: AMS 5616	B	U	U		U	U		U		U	U		
53320	CRES GREEK ASCOLOY WELD METAL QUENCHED & TEMPERED SPEC: AMS 5817	B	U	U		U	U		U		U	U		
53309	CRES GREEK ASCOLOY WIRE COLD FINISHED SPEC: AMS 5616	B	U	U		U	U		U		U	U		
52711	CRES HK AS CASTING	U	U											
52709	CRES HK CAST TUBE CENTRIFUGAL SPEC: ASTM A608	U	U											
52710	CRES HK CASTING ANNEALED	U	U											
52708	CRES HK CASTING HIGH TEMP SERVICE SPEC: ASTM A351	U	U											
53149	CRES N-155 BAR AGED	A	U											
53150	CRES N-155 BAR ANNEALED	A	U											
53148	CRES N-155 CASTINGS PRECISION INVESTMENT AS CAST SPEC: AMS 5376	A	U											
53152	CRES N-155 FORGING AGED	A	U											
53151	CRES N-155 FORGING ANNEALED	A	U											
53154	CRES N-155 PLATE ANNEALED SPEC: AMS 5532	A	U											

MSFC-HDBK-527 REV F ■ 9999942 0004992 8 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53146	CRES N-155 SHEET ANNEALED SPEC: AMS 5532		A	U											
53153	CRES N-155 STRIP ANNEALED SPEC: AMS 5532		A	U											
53155	CRES N-155 TUBE ANNEALED SPEC: AMS 5585		A	U											
53147	CRES N-155 TUBE WELDED ANNEALED SPEC: AMS 5585		A	U											
10464	CRES NITRONIC 60 MANF: ARMCO		A	B	A		A	A		A		A	A		
53117	CRES V-57 BAR AGED 93 KSI		U	U											
53116	CRES V-57 BAR SOLUTION TREATED 172 KSI		U	U											
10661	CRES XM-27 E-BRITE Z6-1 BAR SPEC: ASTM A479		A	A	U		U	U		U		A	U		
50232	CU,PB ANACONDA 129 AV PLATED		U	U	U		U	U		U		U	U		
10484	CUPRON 45% NI 55% CU MANF: SIGMUND COHN CORP		A	U	U		U	U				U	U		
53173	DELETED														
53174	DELETED														
50505	DURONZE III (708)		A	A	U		U	U		U		U	C		
50364	ELGILOY		U	U	A		A	U		U		A	A		
50842	ELGILOY RC55 STRIP SPRING SPEC: MB0170-044	MB0170-102	A	A	A		A	A		X		A	A		
10146	ELGILOY RC55 WIRE SPRING SPEC: MB0170-102	MB0170-044	A	A	A		A	A		X		A	A		
30127	GOLD ALLOY 60AU 35AG 5PT TUBE		A	A	U		U	U		U		A	A		
50099	GOLD WIRE (ELECTRICAL)		A	A	A		A	X		X		U	U		
10632	GOLD-PLATINUM ALLOY B-12% PT		A	A	U		U	U		U		U	U		
30153	GOLD-PT ALLOY		A	A	U		U	U		U		U	U		
30083	HASTELLOY B BAR SPEC: MS0135		A	A	A		A	A		U		U	X		

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50843	HASTELLOY B FORGING SPEC: MS0135		A	A	A		A	A		A		U	X		
10158	HASTELLOY C CASTING INVESTMENT ANNEALED SPEC: AMS 5388		A	A	A	1000	A	A		A		U	X		
50845	HASTELLOY X PLATE SPEC: AMS 5536	AMS 5754	A	A	A		A	A		C		U	X		
10374	HASTELLOY X SHEET SPEC: AMS 5536	AMS 5754	A	A	A		A	A		C		U	X		
50844	HASTELLOY X STRIP SPEC: AMS 5536		A	A	A		A	A		C		U	X		
10297	HAYNES 188 BAR ANNEALED SPEC: AMS 5772		A	A	A		A	A		X		A	A		
10142	HAYNES 188 FOIL ANNEALED SPEC: MBO 170-066		A	A	A		A	A		C		A	A		
50846	HAYNES 188 FORGING ANNEALED SPEC: AMS 5772		A	A	A		A	A		C		A	A		
50847	HAYNES 188 PLATE ANNEALED SPEC: AMS 5608		A	A	A		A	A		X		A	A		
10397	HAYNES 188 SHEET ANNEALED SPEC: AMS 5608	MB0170-103	A	A	A		A	A		X		A	A		
10143	HAYNES 188 TUBE ANNEALED		A	A	A		A	A		C		A	A		
10145	HAYNES 25 BAR ANNEALED SPEC: AMS 5759		A	A	A		A	A		C		A	A		
50848	HAYNES 25 FORGING ANNEALED SPEC: AMS 5759		A	A	A		A	A		C		A	A		
50849	HAYNES 25 PLATE ANNEALED SPEC: AMS 5537		A	A	A		A	A		A		A	A		
10144	HAYNES 25 SHEET ANNEALED SPEC: AMS 5537		A	A	A		A	A		A		A	A		
30095	HAYNES STELLITE 21 INVESTMENT CAST SPEC: AMS 5385		A	A	A		U	A		A		U	U		
30084	HAYNES STELLITE 31 INVESTMENT CAST SPEC: AMS 5382		A	A	A		A	A		X		U	U		
10646	HAYNES STELLITE 6B		A	A	A		A	U		U		U	U		

MSFC-HDBK-527 REV F 9999942 0004994 1

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	NDMH RTG	NDMH TEMP	LOH2 RTG	LH2 RTG	LH2 PRESS	LH2 TEMP
53354	INCOLOY 800 BAR COLD DRAWN & ANNEALED SPEC: ASTM B408	A	A											
53353	INCOLOY 800 BAR HOT FINISHED SPEC: ASTM B408	A	A											
53342	INCOLOY 800 FORGING	A	A											
53345	INCOLOY 800 PIPE 1/2 HARD SPEC: ASTM B407	A	A											
53343	INCOLOY 800 PIPE ANNEALED SPEC: ASTM B407	A	A											
53344	INCOLOY 800 PIPE COLD DRAWN & ANNEALED SPEC: ASTM B407	A	A											
53346	INCOLOY 800 PIPE FULL HARD SPEC: ASTM B407	A	A											
53355	INCOLOY 800 PLATE ANNEALED SPEC: ASTM B409	A	A											
53357	INCOLOY 800 PLATE ANNEALED SPEC: ASTM B409	A	A											
53356	INCOLOY 800 PLATE AS ROLLED SPEC: ASTM B409	A	A											
53352	INCOLOY 800 ROD COLD DRAWN & ANNEALED SPEC: ASTM B408	A	A											
53351	INCOLOY 800 ROD HOT FINISHED SPEC: ASTM B408	A	A											
53358	INCOLOY 800 SHEET AS ROLLED SPEC: ASTM B409	A	A											
53359	INCOLOY 800 SHEET COLD DRAWN & ANNEALED SPEC: ASTM B409	A	A											
53360	INCOLOY 800 STRIP COLD DRAWN & ANNEALED SPEC: ASTM B409	A	A											
53349	INCOLOY 800 TUBE SEAMLESS 1/2 HARD SPEC: ASTM B407	A	A											
53347	INCOLOY 800 TUBE SEAMLESS ANNEALED SPEC: ASTM B407	A	A											
53348	INCOLOY 800 TUBE SEAMLESS COLD DRAWN & ANNEALED SPEC: ASTM B407	A	A											

MSFC-HDBK-527 REV F 9999942 0004995 3

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53350	INCOLOY 800 TUBE SEAMLESS FULL HARD SPEC: ASTM B407	A	A											
53279	INCOLOY 800H BAR AGED	A	A											
53277	INCOLOY 800H BAR ANNEALED	A	A											
53278	INCOLOY 800H BAR COLD WORKED	A	A											
53280	INCOLOY 800H BAR COLD WORKED AND AGED	A	A											
53096	INCOLOY 801 BAR AGED SPEC: AMS 5742	A	A											
53091	INCOLOY 801 FORGING AGED SPEC: AMS 5742	A	A											
53090	INCOLOY 801 FORGING ANNEALED SPEC: AMS 5742	A	A											
53097	INCOLOY 801 JOINT WELDED	A	A											
53092	INCOLOY 801 PLATE ANNEALED SPEC: AMS 5552	A	A											
53098	INCOLOY 801 RINGS FLASH WELDED SPEC: AMS 5742	A	A											
53099	INCOLOY 801 STOCK SPEC: AMS 5742	A	A											
53093	INCOLOY 801 STRIP ANNEALED SPEC: AMS 5552	A	A											
53095	INCOLOY 801 TUBE AGED	A	A											
53094	INCOLOY 801 TUBE WELDED AGED	A	A											
53187	INCOLOY 802 ANNEALED	A	A											
53185	INCOLOY 802 PLATE ANNEALED	A	A											
53189	INCOLOY 802 PLATE ANNEALED & AGED	A	A											
53184	INCOLOY 802 ROUNDS ANNEALED	A	A											
53188	INCOLOY 802 SHAPES ANNEALED & AGED	A	A											
53186	INCOLOY 802 TUBE EXTRUDED ANNEALED	A	A											
53215	INCOLOY BAR ANNEALED	A	A											

MSFC-HDBK-527 REV F 9999942 0004996 5

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDXE RTG	HDXE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53220	INCOLOY BAR COLD DRAWN		A	A											
53218	INCOLOY BAR HOT ROLLED		A	A											
53219	INCOLOY BAR HOT WORKED		A	A											
53214	INCOLOY PLATE ANNEALED		A	A											
53217	INCOLOY PLATE HOT ROLLED		A	A											
53211	INCOLOY SHEET ANNEALED		A	A											
53209	INCOLOY SHEET DEEP DRAWN		A	A											
53213	INCOLOY STRIP ANNEALED		A	A											
53210	INCOLOY STRIP DEEP DRAWN		A	A											
53212	INCOLOY TUBE ANNEALED		A	A											
53216	INCOLOY WIRE ANNEALED		A	A											
10745	INCONEL 100 CASTING INVESTMENT SPEC: AMS 5397		A	A	A		A	A		A		C	X		
10135	INCONEL 600 BAR ANNEALED SPEC: AMS 5665	AMS 7232	A	A	A	1600	A	A		A		C	X		
50855	INCONEL 600 FORGING ANNEALED SPEC: AMS 5665	ASTM B-166	A	A	A		A	A		A		C	X		
50857	INCONEL 600 PLATE ANNEALED SPEC: AMS 5540 MIL-N-6840	ASTM B-168	A	A	A		A	A		A		C	X		
50856	INCONEL 600 RINGS ANNEALED SPEC: AMS 5665	ASTM B-166	A	A	A		A	A		A		C	X		
10134	INCONEL 600 SHEET ANNEALED SPEC: AMS 5540 MIL-N-6840	ASTM B168	A	A	A	1600	A	A		A		C	X		
50858	INCONEL 600 STRIP ANNEALED SPEC: AMS 5540 MIL-N-6840	ASTM B-168	A	A	A		A	A		A		C	X		
10038	INCONEL 600 TUBE ANNEALED SPEC: AMS 5580 MIL-T-7840	ASTM B167	A	A	A	1000	A	A		A		C	X		
10009	INCONEL 600 WIRE ANNEALED SPEC: AMS 5687	QQ-W-390	A	A	A	2000	A	A		A		C	X		

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50859	INCONEL 601 PLATE ANNEALED SPEC: AMS 5870	MB0170-069	A	A	A		A	A		A		C	C		
10140	INCONEL 601 SHEET ANNEALED SPEC: AMS 5870	MB0170-069	A	A	A	1600	A	A		A		C	X		
50860	INCONEL 601 STRIP ANNEALED SPEC: AMS 5870		A	A	A		A	A		A		C	X		
10727	INCONEL 625 BAR SPEC: AMS 5599	AMS 5666	A	A	A		A	A		A		C	X		
10288	INCONEL 625 BAR ANNEALED MANF: ZZ 01 10147 ZZ N2O4 10264		A	A	A		A	A		A		C	X		
50861	INCONEL 625 FORGING ANNEALED		A	A	A		A	A		A		C	X		
50863	INCONEL 625 PLATE SPEC: AMS 5666		A	A	A		A	A		A		C	X		
50862	INCONEL 625 PLATE ANNEALED SPEC: AMS 5599		A	A	A		A	A		A		C	X		
10404	INCONEL 625 SHEET ANNEALED SPEC: AMS 5599		A	A	A		A	A		A		C	X		
10141	INCONEL 625 STRIP ANNEALED SPEC: AMS 5599	MB0170-070	A	A	A		A	A		A		C	X		
10403	INCONEL 625 TUBE ANNEALED SPEC: ASTM B444		A	A	A		A	A		A		C	X		
10280	INCONEL 706 BAR STA SPEC: AMS 5701	AMS 5703	A	A	A	1000	A	A		X		C	X		
50879	INCONEL 706 FORGING STA SPEC: AMS 5703		A	A	A		A	A		X		C	X		
50877	INCONEL 706 PLATE SPEC: AMS 5605		A	A	A		A	A		X		C	X		
50880	INCONEL 706 RINGS STA SPEC: AMS 5703		A	A	A		A	A		X		C	X		
10209	INCONEL 706 SHEET SPEC: AMS 5605		A	A	A		A	A		A		C	X		
50878	INCONEL 706 STRIP SPEC: AMS 5605		A	A	A		A	A		A		C	X		

MSFC-HDBK-527 REV F 9999942 0004998 9

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10406	INCONEL 718 BAR SPEC: AMS 5663		A	A	A	3300	A	A		A		A	X		
10332	INCONEL 718 BAR CEVM SPEC: MB0170-041		A	A	A		A	A		A		A	X		
10129	INCONEL 718 BAR ST1750F SPEC: MB0170-075		A	A	A	3300	A	A		A		A	X		
10127	INCONEL 718 BAR ST1900F SPEC: MB0170-076		A	A	A		A	A		A		A	X		
10452	INCONEL 718 CASTING ST1900 SPEC: RB0170-155		A	A	A		A	A		A		A	X		
50881	INCONEL 718 FORGING CEVM SPEC: MB0170-041		A	A	A		A	A		A		A	X		
50874	INCONEL 718 FORGING ST1750F SPEC: MB0170-075		A	A	A		A	A		A		A	X		
10505	INCONEL 718 FORGING ST1775F SPEC: AMS 5662	AMS 5664	A	A	A		A	A		A		A	X		
50871	INCONEL 718 FORGING ST1900F		A	A	A		A	A		A		A	X		
50882	INCONEL 718 PLATE CEVM 1900F SPEC: MB0170-040		A	A	A		A	A		A		A	X		
50884	INCONEL 718 PLATE ST1750F SPEC: MB0170-074		A	A	A		A	A		A		A	X		
50886	INCONEL 718 PLATE ST1900F SPEC: MB0170-071		A	A	A		A	A		A		A	X		
50875	INCONEL 718 RING ST1750F SPEC: MB0170-075		A	A	A		A	A		A		A	X		
50873	INCONEL 718 RINGS ST1775F SPEC: AMS 5662	AMS 5664	A	A	A		A	A		A		A	X		
50872	INCONEL 718 RINGS ST1900F		A	A	A		A	A		A		A	X		
10331	INCONEL 718 SHEET CEVM STA1900F SPEC: MB0170-040		A	A	A		A	A		A		A	X		
10128	INCONEL 718 SHEET ST1750 SPEC: MB0170-074		A	A	A	3300	A	A		A		A	X		
10126	INCONEL 718 SHEET ST1900 SPEC: MB0170-071		A	A	A	3300	A	A		A		A	X		

MSFC-HDBK-527 REV F ■ 9999942 0004999 0 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50883	INCONEL 718 STRIP CEVM ST1900F SPEC: MB0170-040		A	A	A		A	A		A		A	X		
50885	INCONEL 718 STRIP ST1750F SPEC: MB0170-074		A	A	A		A	A		A		A	X		
50887	INCONEL 718 STRIP ST1900F SPEC: MB0170-071		A	A	A		A	A		A		A	X		
10287	INCONEL 718 TUBE MANF: ZZ 01 10147 ZZ N2O4 10264 SPEC: AMS 5589		A	A	A	3300	A	A		A		A	X		
10286	INCONEL 718 TUBE ST1950F SPEC: AMS 5590		A	A	A	3300	A	A		A		A	X		
30116	INCONEL 903 SHEET,PLATE,STRIP SPEC: RB0170-196		A	A	U		U	U		U		U	U		
10139	INCONEL X750 BAR STA SPEC: AMS 5667	MIL-N-8550	A	A	A	3300	A	A		A		C	X		
50852	INCONEL X750 FORGING STA SPEC: AMS 5667	MIL-N-8550	A	A	A		A	A		A		C	X		
50851	INCONEL X750 PLATE ANNEALED SPEC: AMS 5542	AMS 5598	A	A	A		A	A		A		C	X		
50854	INCONEL X750 PLATE STA SPEC: AMS 5542		A	A	A		A	A		A		C	X		
50853	INCONEL X750 RINGS STA SPEC: AMS 5667	MIL-N-8550	A	A	A		A	A		A		C	X		
10450	INCONEL X750 SHEET ANNEALED SPEC: AMS 5542	AMS 5598	A	A	A		A	A		X		C	X		
10138	INCONEL X750 SHEET STA SPEC: MIL-N-7786		A	A	A	3300	A	A		A		C	X		
10136	INCONEL X750 STRIP EXTRUDED SPEC: AMS 5542 MIL-N-7786	AMS 5598	A	A	A	3300	A	A		A		C	X		
10400	INCONEL X750 STRIP STA SPEC: AMS 5542	ASTM B168	A	A	A	3300	A	A		A		C	X		
10695	INCONEL X750 WIRE SPRING STA SPEC: MB0160-047 TY 1		A	A	A		A	A		A		C	X		

MSFC-HDBK-527 REV F 9999942 0005000 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	NDZE RTG	NDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10327	INDIUM (99.94%) MANF: INDIUM CORP OF AMER.		A	A	U		U	U		U		U	U		
10314	INVAR 36 BAR (GLASS SEALING) SPEC: MIL-I-23011 CL7	MIL-S-16598	B	A	A		A	X		X		C	X		
10723	IRIDIUM MANF: INT NICKEL CO		A	A	U		U	U		U		U	U		
10749	IRON-MALLEABLE SPEC: ASTM A-47/A-197		B	A	U		U	U		U		U	U		
30118	K-6 ALLOY PLATING NI PB CR SPEC: ME261-0033		A	A	B		A	U		U		A	U		
30141	LEAD ALLOY 6.5SB .5SN CASTING SPEC: AMS 7720	QQ-L-171	A	A	U		U	U		U		U	U		
10630	LEDLOY-A STEEL (180-200KSI)		B	B	U		U	U		U		U	U		
30154	MAGNESIUM ALLOY PHOTO GRADE		B	A	U		U	U		U		U	U		
10689	MAGNET 17CO-83FE ALLOY SPEC: LTV-RFCA		B	A	A		A	X		X		U	U		
10250	MAGNET 50NI 50FE BAR SPEC: AMS 7718		B	A	A	1600	A	A		X		X	X		
50867	MAGNET 50NI 50FE FORGING SPEC: AMS 7718		B	A	A		A	A		X		X	X		
50868	MAGNET 50NI 50FE TUBE SPEC: AMS 7718		B	A	A		A	A		X		X	X		
10473	MAGNET 79NI 4MO 17FE PERMALLOY		B	A	A		A	A		X		X	X		
10697	MAGNET ALLEGHENY LUDLUM SPEC: ARMCO 72-82-M22		B	A	A		A	X		X		U	U		
10270	MAGNET ALNICO V. VI. VIII SPEC: MIL-M-46888		B	A	A		A	X		X		A	U		
10269	MAGNET ARMCO INGOT IRON SPEC: MIL-I-11695		B	A	A		A	X		X		U	U		
50133	MAGNET CERAMIC INDOX		A	A	U		U	U		U		U	U		
10235	MAGNET HI-PERM MUMETAL SPEC: AMS 7701		B	A	A		A	A		X		X	X		
50865	MAGNET NI-FE ALLOY BAR SPEC: MIL-N-14411 C1-2-3		B	A	A		A	A		X		X	X		

MSFC-HDBK-527 REV F 9999942 0005001 3

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10131	MAGNET NI-FE ALLOY BAR NI77 CU5 CR1.5 SPEC: AMS 7705		B	A	A	1600	A	A		X		X	X		
50888	MAGNET NI-FE ALLOY FORGING NI77 CU5 CR1.5 SPEC: AMS 7705		B	A	A		A	A		X		X	X		
51171	MAGNET NI-FE ALLOY PLATE SPEC: AMS 7719		B	A	A		A	A		X		X	X		
10442	MAGNET NI-FE ALLOY ROD SPEC: MIL-I-23011 C2	MIL-N-22840	B	A	A		A	A		X		X	X		
10215	MAGNET NI-FE ALLOY SHEET SPEC: AMS 7719 MIL-N-14411 C2	MIL-N-14411 C1 MIL-N-14411 C3	B	A	A	1600	A	A		X		X	X		
10118	MAGNET NI-FE SHEET MUMETAL SPEC: AMS 7701		B	A	A	1600	A	A		X		X	X		
50866	MAGNET NI-FE STRIP MUMETAL SPEC: AMS 7701		B	A	A		A	A		X		X	X		
50132	MAGNET SAMARIUM COBALT		A	U	U		U	U		U		U	U		
30138	MAGNET SM CO (MC203-0002)		A	A	U		U	U		U		U	U		
30157	MAGNET SUPERPERM 80NI4MO16FE		B	A	U		U	U		U		U	U		
10722	MAGNET VICALLOY 10V52CO38FE		B	A	A		A	X		X		U	U		
50234	MANGANESE ZINC BEADS MANF: FAIR-RITE		U	U	U		U	U		U		U	U		
10748	MANGANIN 87CU-13MN		A	U	A		A	X		X		A	A		
50187	MAR-M246 SPEC: RB0170-157 RB0170-236	RB0170-166	U	U	A		A	U		U		U	U		
30161	MARAGING 18% STEEL >200KSI SPEC: MIL-S-46850		B	C	U		U	U		U		X	X		
52766	MARAGING 18NI (200) PLATE STEEL AGED SPEC: ASTM A538		B	C											
52758	MARAGING 18NI (200) PLATE STEEL AGED AIR MELT SPEC: ASTM A538		B	C											
52759	MARAGING 18NI (200) PLATE STEEL AGED VAC REMELT SPEC: ASTM A538		B	C											

MSFC-HDBK-527 REV F 9999942 0005002 5

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52763	MARAGING 18NI (200) ROUNDS STEEL AGED SPEC: ASTM A538		B	C											
52764	MARAGING 18NI (200) SHEET STEEL AGED SPEC: ASTM A538		B	C											
52757	MARAGING 18NI (200) SHEET STEEL AGED VAC REMELT SPEC: ASTM A538		B	C											
52765	MARAGING 18NI (200) STEEL AGED SPEC: ASTM A538		B	C											
52760	MARAGING 18NI (200) STEEL AGED AIR MELT HEAVY SPEC: ASTM A538		B	C											
52761	MARAGING 18NI (200) STEEL AGED VAC ARC REMELT SPEC: ASTM A538		B	C											
52762	MARAGING 18NI (200) STEEL ANNEALED SPEC: AMS 6520	ASTM A538	B	C											
52767	MARAGING 18NI (200) STEEL PLATE WELDED AND AGED SPEC: ASTM A538		B	C											
10647	MARAGING STEEL 250>200KSI SPEC: MIL-S-46850		B	C	A		A	U		U		X	X		
30162	MARAGING VASCO MAX 300 STEEL SPEC: MIL-S-46850		B	C	U		U	U		U		U	U		
10747	MERCURY		X	N	U		U	U		U		U	U		
30100	MOLYBDENUM SPEC: ASTM B 387		B	A	U		U	A		X		U	U		
10222	MONEL 400 67NI 30CU WIRE ANNEALED SPEC: AMS 4730 QQ-N-281 SANDVIK 11R50	LB0170-103I&II RR-W-360	A	A	A		A	A		X		U	X		
50305	MONEL 405		A	A	A		A	A		X		U	X		
10740	MONEL K-500 ALLOY SPEC: AMS 4676	QQ-N-286	A	A	A		A	A		X		U	X		
51078	MP 159 SPEC: AMS 5842		A	A											
10123	MULTIPHASE MP35N SPEC: AMS 5758		A	A	A		A	U		U		A	A		

MSFC-HDBK-527 REV F 9999942 0005003 7

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	LH2 RTG	LH2 PRESS	LH2 TEMP
10742	NI-AL-FE-CU ALLOY SPEC: QQ-N-286		A	A	A		A	A		X		U	X		
10488	NI80 20FE CO-NETIC AA ALLOY MANF: PERFECTION MICA CO		A	A	U		U	U		U		U	U		
10524	NICHROME 80NI-20CR MANF: JM NEY CO		A	A	A		U	A		U		U	U		
10225	NICKEL 200 SHEET LOW CARBON SPEC: AMS 5553 ASTM B161	ASTM B160 ASTM B162	A	A	A	3000	A	A		A		U	U		
50890	NICKEL 200 STRIP LOW CARBON SPEC: AMS 5553 ASTM B-162	ASTM B-160	A	A	A		A	A		A		U	U		
50891	NICKEL 201 SHEET LOW CARBON SPEC: AMS 5553 ASTM B-161	ASTM B-160 ASTM B-162	A	A	A		A	A		A		U	U		
50892	NICKEL 201 STRIP LOW CARBON SPEC: AMS 5553 ASTM B-161	ASTM B-160 ASTM B-162	A	A	A		A	A		A		U	U		
30145	NICKEL 30CR 3AL 3FE SPEC: KARMA		A	A	U		U	U		U		U	U		
10320	NICKEL 99% ELECTROFORMED PARTS SPEC: LB0170-107		A	A	A		A	A		X		U	X		
10637	NICKEL ALLOY 20CR3AL2CO75NI		A	A	U		U	U		U		U	U		
10477	NICKEL ALLOY 42 (GLASS SEALING) MANF: WILKINSON CO		A	A											
10495	NICKEL ALLOY 52 (GLASS SEALING)		A	A	A		A	U		U		X	X		
30069	NICKEL ALLOY 53 (GLASS SEALING) SPEC: AMS 7726 AMS 7728	AMS 7727 MIL-I-23011 CL1	A	U	U		U	X		U		U	U		
10441	NICKEL ALLOY 902 SPAN-C SPEC: AMS 5221	AMS 5225	A	A	A		A	A		A		C	X		
10363	NICKEL BAR (ELECTRONIC) SPEC: MIL-N-46025		A	A	A		A	A		X		U	X		
50869	NICKEL FL WIRE (ELECTRONIC) SPEC: MIL-N-46025		A	A											

MSFC-HDBK-527 REV F
9999942 0005004 9
Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	NDMH RTG	NDMH TEMP	LOH2 RTG	MMH2 RTG	MMH2 PRESS	MMH2 TEMP
50870	NICKEL STRIP (ELECTRONIC) SPEC: MIL-N-46025		A	A											
10132	NICKEL U-500 ST BAR SPEC: AMS 5753		A	A	A		A	U		X		U	U		
50876	NICKEL U-500 ST FORGING SPEC: AMS 5753		A	A	A		A	U		X		U	U		
50508	NILSTAIN BRIDGEWIRE MANF: WILBUR DRIVER CO		A	U	U		U	U		U		U	U		
53242	NITRALLOY 135MOD BAR COLD ROLLED SPEC: AMS 6470		B	B	U		U	X		X		U	U		
53241	NITRALLOY 135MOD BAR HOT ROLLED SPEC: ASTM 6470 MIL-S-6709	ASTM A355	B	B	U		U	X		X		U	U		
53245	NITRALLOY 135MOD BAR QUENCHED & NITRIDED SPEC: MIL-S-6709		B	B	U		U	X		X		U	U		
53243	NITRALLOY 135MOD FORGING SPEC: AMS 6470	MIL-S-6709	B	B	U		U	X		X		U	U		
53244	NITRALLOY 135MOD FORGING STOCK SPEC: ANS 6470	MIL-S-6709	B	B	U		U	X		X		U	U		
30063	NITRALLOY 135MOD QUENCHED AND TEMPERED BAR SPEC: AMS 6470	MIL-S-6709	B	B	U		U	X		X		U	U		
50514	NITRONIC 40		A	A	U		U	A		A		U	U		
10608	PALINEY #7 COMP D SPEC: AMS 7735 MIL-E-46065 COMP D	ASTM B5SS	A	A	U		U	U		U		U	U		
10713	PALINEY 6 PD-PT-AG-CU ALLOY MANF: J M NEY CO SPEC: ASTM B 563		A	A	U		U	U		U		U	U		
10494	PALLADIUM 25% SILVER ALLOY MANF: MATTHEY BISHOP		A	A	U		U	U		X		A	U		
10628	PALLADIUM BLACK 99.95%PD		A	N	U		U	U		U		U	U		
50233	PERMALLOY NI-FE ALLOY		U	U											
10618	PERMENDUR 49CO 2V 49FE		A	A	U		U	U		U		U	U		
50124	PLATING CADMIUM SPEC: AMS 2400	QQ-P-416	A	N	A		A	X		X		U	U		

MSFC-HDBK-527 REV F 9999942 0005005 0

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
30082	PLATING CADMIUM ELECTRODEPOSIT SPEC: AMS 2400 MIL-C-8837 QQ-P-416 TY2	MIL-C-81562 MIL-V-83976	A	N	U		A	X		X		U	U		
30148	PLATING CADMIUM/TITANIUM		A	N	U		A	X		X		U	U		
10275	PLATING CHROMIUM CLASS 2 SPEC: QQ-C-320		A	N	A		A	A		X		A	A		
50188	PLATING CHROMIUM GLASS		U	N	A		A	U		U		U	U		
10311	PLATING COPPER ELECTRODEPOSIT SPEC: AMS 2418	MIL-C-14550	A	N	A	2700	A	X		X		U	U		
10328	PLATING GOLD SPEC: MIL-G-45204		A	N	A	3000	A	X		X		A	A		
50141	PLATING NICKEL SPEC: MIL-STD-868 T1		A	N	A		A	A		U		U	U		
10308	PLATING NICKEL ELECTRODEPOSIT SPEC: AMS 2403 MIL-P-18317	MA0109-311 QQ-N-290	A	N	A	3000	A	A		U		A	X		
10046	PLATING NICKEL ELECTROLESS SPEC: AMS 2404	MIL-C-26074	A	N	A	3000	A	A		U		A	X		
30190	PLATING NICKEL-CHROMIUM		A	N	A		A	A		A		A	A		
30191	PLATING NICKEL-GOLD		A	N	A		A	X		X		A	A		
10274	PLATING NIICKEL TIN ELECTROLESS SPEC: MB0125-041		A	N	X		A	A		X		U	U		
30128	PLATING RHODIUM ELECTRODEPOSIT SPEC: MIL-R-46085		A	N	U		U	U		U		U	U		
10039	PLATING SILVER SPEC: MA0109-313	QQ-S-365	A	N	A		A	X		C		X	X		
10281	PLATING SILVER FASTENERS ONLY SPEC: AMS 2411	QQ-S-365	A	N	A		A	X		X		X	X		
10312	PLATING TIN SPEC: AMS 2408 MIL-T-10727	MIL-F-14072	A	N	X		A	A		X		C	C		
50108	PLATING TIN LEAD (ELEC-DEPOSIT SPEC: MIL-P-81728		A	N	X		A	X		X		C	C		

MSFC-HDBK-527 REV F 9999942 0005006 2

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDIE RTG	HDIE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
30143	PLATING ZINC		A	N	U		U	U		U		U	U		
30115	PLATINUM & PLATINUM ALLOY		A	A	U		U	U		U		U	U		
10629	PLATINUM BLACK (PT POWDER)		A	N	U		U	U		U		U	U		
10703	PLATINUM-COBALT ALLOY SPEC: QQ-P-428		A	A	U		U	U		U		U	U		
10746	RA 330 NI-CR-FE-SI ALLOY SPEC: AMS 5592		A	A	A		A	A		A		A	A		
53101	RA-330HC ALLOY BAR ANNEALED		A	A	A		A	A		A		A	A		
53100	RA-330HC ALLOY PLATE ANNEALED		A	A	A		A	A		A		A	A		
53102	RA-330HC ALLOY STOCK ANNEALED		A	A	A		A	A		A		A	A		
10373	RENE 41 BAR SPEC: AMS 5712	AMS 5713	A	A	U		A	U		U		U	U		
50893	RENE 41 FORGING SPEC: AMS 5713	ASM 5712	A	A	U		A	U		U		U	U		
50896	RENE 41 PLATE SPEC: AMS 5545		A	A	U		A	U		U		U	U		
50894	RENE 41 RINGS SPEC: AMS 5712	AMS 5713	A	A	U		A	U		U		U	U		
10446	RENE 41 SHEET SPEC: AMS 5545		A	A	U		A	U		U		U	U		
50895	RENE 41 STRIP SPEC: AMS 5545		A	A	U		A	U		U		U	U		
30085	RENE 95 BAR SPEC: CM24.14-01		A	A	U		U	U		U		U	U		
50898	RENE 95 FORGING SPEC: CM24.14-01		A	A	U		A	U		U		U	U		
50897	RENE 95 SHAPE SPEC: CM24.14-01		A	A	U		A	U		U		U	U		
30187	SILICON		A	U	U		U	U		U		U	U		
10433	SILVER		A	A	A		A	X		X		X	X		
30146	SILVER 18% NICKEL ALLOY		A	A	U		U	U		U		X	X		

MSFC-HDBK-527 REV F 9999942 0005007 4

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10338	SOLDER 1.5% SILVER SPEC: QQ-S-571	A	N	U		U	X		X		U	U		
10616	SOLDER 28SN 44PB 28BI	A	N	X		Z	U		U		U	U		
30132	SOLDER 34SN 63PB 3ZN	A	N	A		Z	X		X		U	U		
10654	SOLDER 5.5AG SPEC: QQ-S-571	A	N	B		B	X		X		U	U		
30171	SOLDER 51SN 30PB 18CD MANF: B F GOODRICH	A	N	X		Z	X		X		U	U		
50189	SOLDER 5AG.16.6ZN 78.4CD MANF: HANDY AND HARMON	U	N	A		Z	U		U		U	U		
10449	SOLDER 5SB SPEC: QQ-S-571	A	U	U		U	X		X		U	U		
10690	SOLDER 5SN 95PB SPEC: QQ-S-571	A	N	B		B	U		U		U	U		
50300	SOLDER 60SN WRAP 2	U	N	X		A	X		X		U	U		
10491	SOLDER 70SN 30PB SPEC: MIL-P-81728	A	N	X		A	U		U		U			
10704	SOLDER 80AU 20SN	A	N	X		A	U		U		U	U		
10667	SOLDER 95SN 5AG	A	N	X		Z	X		X		U	U		
10448	SOLDER 96SN SPEC: QQ-S-571	A	N	X		Z	X		X		U	U		
10627	SOLDER ALPHA 111 PB-SN-18CD	A	N	X		A	U		U		U	U		
30168	SOLDER CERTANIUM 36EC MANF: CERTANIUM	A	N	U		U	U		U		U	U		
30156	SOLDER EUTEC 157	A	N	U		U	U		U		U	U		
10711	SOLDER INDALOY # 2 MANF: INDIUM CORP	A	N	U		U	U		U		U	U		
50511	SOLDER SILVER CASTOLIN 1030	A	N	U		U	U		U		U	U		
10626	SOLDER SN 10 SPEC: QQ-S-571	A	N	X		A	U		U		U	U		
10683	SOLDER SN 20 SPEC: QQ-S-571	A	N	X		Z	U		U		U	U		

MSFC-HDBK-527 REV F ■ 9999942 0005008 6 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	NDMH RTG	NDMH TEMP	LOH2 RTG	NIH2 RTG	NIH2 PRESS	NIH2 TEMP
10206	SOLDER SN 40 WRAP 4 SPEC: QQ-S-571		A	N	X		Z	X		X		U	U		
10079	SOLDER SN 50/60/62/63 SPEC: QQ-S-571		A	N	X		Z	X		X		A	U		
50231	SOLDER SN 60 SPEC: QQ-S-571		A	N	X		A	U		U		U	U		
10417	SPRING ALLOY COMP 2 TYPE1 WIRE		B	N	A		A	U		X		X	X		
10653	STEEL 0.90-1.30 CARBON BAR <180 SPEC: AMS 5132		B	A	A		A	X		U		A	A		
10648	STEEL 1008-1020 <180 KSI SPEC: FED-STD-66		B	A	A		A	X		U		A	A		
50131	STEEL 1009-1050 <180 KSI SPEC: QQ-S-698		B	A	A		A	X		X		A	A		
10358	STEEL 1010 <180KSI SPEC: ASTM A366/A366M	QQ-W-461	B	A	A		A	X		X		A	A		
10359	STEEL 1010 TO 1040 SPEC: QQ-S-630 QQ-S-633 QQ-S-637	QQ-S-631 QQ-S-634	B	A	A		A	X		X		A	A		
50901	STEEL 1020 PLATE <180 KSI SPEC: QQ-S-698		B	A	U		U	X		X		X	X		
50113	STEEL 1020 SHEET <180 KSI SPEC: MIL-S-7952	QQ-S-698	B	A	U		U	X		X		A	A		
52702	STEEL 1025 BAR ALL SPEC: MIL-S-7097		B	N											
50903	STEEL 1025 PLATE <180 KSI SPEC: QQ-S-698		B	A											
50902	STEEL 1025 SHEET <180 KSI SPEC: QQ-S-698		B	A											
52699	STEEL 1025 SHEET COLD ROLLED SPEC: MIL-S-7952		B	N											
52700	STEEL 1025 STRIP COLD ROLLED SPEC: MIL-S-7952		B	N											
52701	STEEL 1025 TUBE COLD ROLLED SPEC: MIL-T-5066		B	N											

MSFC-HDBK-527 REV F 9999942 0005009 8

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50904	STEEL 1050 PLATE >180 KSI	B	B	A		A	X		X		U	A		
50246	STEEL 1050 SHEET >180 KSI	B	B	A		A	X		X		U	A		
50905	STEEL 1050 STRIP >180 KSI	B	B	A		A	X		X		U	A		
30142	STEEL 1095 (SPRING) SPEC: ASTM A228/ASS8M	B	A	U		U	X		U		U	U		
10299	STEEL 1095 CONDITION 2 <200KSI SPRING SPEC: MIL-S-7947	B	A	X		A	X		X		X	X		
50523	STEEL 1113 COLD FINISH <180KSI SPEC: FED-STD-66	B	A	U		A	X		X		U	U		
50522	STEEL 1117 COLD FINISH <180KSI SPEC: FED-STD-66	B	A	U		A	X		X		U	U		
30064	STEEL 1213 COLD FINISH <180KSI SPEC: ASTM A108	B	A	U		A	X		X		U	U		
30065	STEEL 1215 COLD FINISH <180KSI SPEC: ASTM A108	B	A	U		A	X		X		U	U		
10731	STEEL 1340 (180-200 KSI)	B	N	A		A	X		X		A	A		
50906	STEEL 17-22A	B	N	A		A	X		X		X	X		
10726	STEEL 17-22A BAR FORGING TUBE SPEC: AMS 6304	B	B	A		A	X		X		X	X		
30104	STEEL 200-220 KSI	B	C	A		A	X		X		X	X		
52620	STEEL 300M BAR 270-300 KSI UTS SPEC: AMS 6419 MIL-S-8844	B	C											
52626	STEEL 300M BILLET 270-300 KSI UTS SPEC: MIL-S-8844	B	C											
52623	STEEL 300M CONSUMABLE VACUUM MELTED 270-300 KSI UTS SPEC: MIL-S-8844	B	C											
52621	STEEL 300M FORGING 270-300 KSI UTS SPEC: AMS 6419 MIL-S-8844	B	C											
52624	STEEL 300M MACHINED FORGING 270-300 KSI UTS SPEC: MIL-S-8844	B	C											
52622	STEEL 300M TUBE 270-300 KSI UTS SPEC: MIL-S-8844	B	C											

MSFC-HDBK-527 REV F 9999942 0005010 4

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	MDXE RTG	MDXE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52625	STEEL 300M WIRE 270-300 KSI UTS SPEC: MIL-S-8844		B	C											
50118	STEEL 4130 180-200KSI SPEC: MIL-S-18729		B	B	A		A	X		X		X	X		
10109	STEEL 4130 BAR 125-180 KSI SPEC: AMS 6350	MIL-S-6758	B	A	A		A	X		X		X	X		
50911	STEEL 4130 FORGING 125-180 KSI SPEC: AMS 6350	MIL-S-6758	B	A	A		A	X		X		X	X		
50912	STEEL 4130 PLATE 125-180 KSI SPEC: AMS 6350	MIL-S-18729	B	A	A		A	X		X		X	X		
10108	STEEL 4130 SHEET 120-180 KSI SPEC: AMS 6350	MIL-S-18729	B	A	A		A	X		X		X	X		
10300	STEEL 4130 TUBE 125-180 KSI SPEC: MIL-T-6736		B	A	A		A	X		X		X	X		
53163	STEEL 4135 ALL 125 KSI UTS		B	A	A		A	X		X		X	X		
53164	STEEL 4135 ALL 150 KSI UTS		B	A	A		A	X		X		X	X		
53165	STEEL 4135 ALL 180 KSI UTS		B	A	A		A	X		X		X	X		
53158	STEEL 4135 PLATE NORMALIZED SPEC: AMS 6352		B	A	A		A	X		X		X	X		
53160	STEEL 4135 ROUND QUENCHED & TEMPERED SPEC: AMS 6365		B	A											
53156	STEEL 4135 SHEET NORMALIZED SPEC: AMS 6352		B	A	A		A	X		X		X	X		
53161	STEEL 4135 SHEET QUENCHED & TEMPERED SPEC: AMS 6352		B	A	A		A	X		X		X	X		
53157	STEEL 4135 STRIP NORMALIZED SPEC: AMS 6352		B	A	A		A	X		X		X	X		
53159	STEEL 4135 TUBE NORMALIZED SPEC: AMS 6372		B	A	A		A	X		X		X	X		
53162	STEEL 4135 TUBE QUENCHED & TEMPERED SPEC: AMS 6372		B	A	A		A	A		A		A	A		
10153	STEEL 4140 150KSI CASTING INVESTMENT SPEC: MIL-S-22141		B	A	A		A	X		X		X	X		

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10122	STEEL 4140 BAR <201 KSI SPEC: AMS 6382	MIL-S-5626	B	B	A		A	X		X		X	X		
30086	STEEL 4140 BAR DIE DRAWN 180 KSI		B	B	A		A	X		X		X	X		
50913	STEEL 4140 FORGING <201 KSI SPEC: AMS 6382	MIL-S-5626	B	B	A		A	X		X		X	X		
50914	STEEL 4140 RING <201 KSI SPEC: AMS 6382	MIL-S-5626	B	B	A		A	X		X		X	X		
53179	STEEL 4330SI ALL 125 KSI UTS		B	A	A		A	X		X		X	X		
53180	STEEL 4330SI ALL 150 KSI UTS		B	A	A		A	X		X		X	X		
53181	STEEL 4330SI ALL 180 KSI UTS		B	B	A		A	X		X		X	X		
53182	STEEL 4330SI ALL 200 KSI UTS		B	B	A		A	X		X		X	X		
53183	STEEL 4330SI ALL 220 KSI UTS		B	C	A		A	X		X		X	X		
53178	STEEL 4330SI SHEET QUENCHED & TEMPERED SPEC: AMS 6407		B	A	A		A	X		X		X	X		
53177	STEEL 4330SI WROUGHT QUENCHED & TEMPERED SPEC: AMS 6407		B	A	A		A	X		X		X	X		
10110	STEEL 4330V BAR >200 KSI SPEC: MIL-S-8699		B	B	A		A	X		X		X	X		
50915	STEEL 4330V FORGING >200 KSI		B	B	A		A	X		X		X	X		
30165	STEEL 4330V QUENCHED & TEMPERED 180-200 SPEC: AMS 6427	MIL-S-8699	C	C	A		A	X		X		X	X		
10154	STEEL 4340 180KSI CASTING INVESTMENT SPEC: MIL-S-22141		B	B	A		A	X		X		X	X		
10114	STEEL 4340 BAR 180-200 KSI SPEC: MIL-S-5000		B	B	A		A	X		X		X	X		
10341	STEEL 4340 BAR > 200KSI SPEC: MIL-S-8844 CL 1		B	B	A		A	C		X		X	X		
50070	STEEL 4340 BAR ANNEALED SPEC: AMS 6414 MIL-S-8844	AMS 6415	B	N	U		U	X		X		X	X		
50922	STEEL 4340 FORGING 180-200 KSI SPEC: AMS 6415	MIL-S-5000	B	B	A		A	X		X		X	X		

MSFC-HDBK-527 REV F 9999942 0005012 8

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	NDZH RTG	NDZH TEMP	LOH2 RTG	NIH2 RTG	NIH2 PRESS	NIH2 TEMP
50920	STEEL 4340 FORGING >200 KSI SPEC: AMS 6414	MIL-S-8844 C1	B	B	U		U	X		X		X	X		
50916	STEEL 4340 FORGING ANNEALED SPEC: AMS 6414 MIL-S-8844	MIL-S-5000	B	N	U		U	X		X		X	X		
50924	STEEL 4340 PLATE >200 KSI SPEC: AMS 6359		B	B	U		U	X		X		X	X		
50921	STEEL 4340 TUBE >200 KSI SPEC: AMS 6414	MIL-S-8844 C1	B	B	U		U	X		X		X	X		
50917	STEEL 4340 TUBE ANNEALED SPEC: AMS 6414		B	N	U		U	X		X		X	X		
50054	STEEL 4344 SHEET ANNEALED SPEC: AMS 6359	MIL-S-8844	B	N	A		A	X		X		X	X		
10284	STEEL 4620 BAR 165KSI SPEC: AMS 6294		B	A	A	2600	A	X		X		X	X		
50123	STEEL 4XXX 200 KSI UTS		B	C	A		A	X		X		U	U		
50145	STEEL 4XXX <180 KSI UTS		B	A	A		A	X		X		U	U		
10513	STEEL 4XXX <200 KSI SPEC: FED-STD-66		B	C	A		A	X		X		X	X		
50110	STEEL 4XXX >200 KSI SPEC: FED-STD-66		B	C	A		A	U		U		U	U		
50135	STEEL 4XXX BOLT >200 KSI SPEC: MIL-B-6812		B	C	A		A	U		U		U	U		
30139	STEEL 4XXX CASTING INVESTMENT >200 KSI SPEC: MIL-S-22141 MIL-S-8844	MIL-S-5000	B	C	A		A	X		X		X	X		
10737	STEEL 50100 BAR 180-200 KSI SPEC: AMS 6442		B	B	A		A	U		X		X	X		
50519	STEEL 50100 BEARING 180-200 KSI SPEC: AMS 6442		B	B	A		A	U		X		X	X		
50925	STEEL 50100 FORGING 180-200 KSI SPEC: AMS 6442		B	B	A		A	U		X		X	X		
10107	STEEL 52100 BAR 180-200 KSI		B	B	A	1500	A	U		X		X	X		
50926	STEEL 52100 FORGING 180-200 KSI SPEC: AMS 7440	MIL-S-7420	B	B	A		A	U		X		X	X		

MSFC-HDBK-527 REV F 9999942 0005013 T

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50518	STEEL 52100 TUBE 180-200 KSI SPEC: AMS 6440		B	B	A		A	U		X		X	X		
30079	STEEL 6150 (RC 46-50) SPEC: FSCM05341SPRING		B	C	U		U	U		U		U	U		
10492	STEEL 6150 50C 1CR 25V SPEC: AMS 6455		B	C	U		U	U		U		U	U		
10617	STEEL 6150 BAR >200 KSI SPEC: MIL-S-8503		B	C	U		U	U		U		U	U		
10511	STEEL 8620 BAR SPEC: MIL-S-7420(E52100)	MIL-S-8690(8620)	B	C	A		A	U		X		X	X		
30074	STEEL 8620 BAR CAS-HD >200 KSI SPEC: AMS 6274		B	C	U		U	U		U		U	U		
50521	STEEL 8620 CAS-HD FORGING >200 KSI SPEC: AMS 6274		B	C	U		U	U		U		U	U		
50520	STEEL 8620 CAS-HD TUBE >200 KSI SPEC: AMS 6274		B	C	U		U	U		U		U	U		
30133	STEEL 8630 BAR >200 KSI SPEC: MIL-S-6050		B	C	U		U	U		U		U	U		
53193	STEEL 8735 BARS SPEC: AMS 6320		B	C											
53194	STEEL 8735 FORGING SPEC: AMS 6320		B	C											
53192	STEEL 8735 PLATE NORMALIZED SPEC: AMS 6357		B	C											
53197	STEEL 8735 ROUNDS <180 KSI UTS SPEC: AMS 6320		B	C											
53196	STEEL 8735 SHEET <180 KSI UTS SPEC: AMS 6357		B	C											
30087	STEEL 8735 SHEET >200 KSI SPEC: FED-STD-66		B	C	U		U	U		U		U	U		
53190	STEEL 8735 SHEET NORMALIZED SPEC: AMS 6357		B	C											
53191	STEEL 8735 STRIP NORMALIZED SPEC: AMS 6357		B	C											

MSFC-HDBK-527 REV F 9999942 0005014 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZK RTG	HDZK TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53198	STEEL 8735 TUBE <180 KSI UTS SPEC: AMS 6535		B	C											
53195	STEEL 8735 TUBE NORMALIZED SPEC: AMS 6282	AMS 6535	B	C											
53175	STEEL 8740 ALL 180 KSI UTS		B	C											
53176	STEEL 8740 ALL 200 KSI UTS		B	C											
53169	STEEL 8740 BAR <200 KSI UTS SPEC: MIL-S-6049A		B	C											
30096	STEEL 8740 BAR >200 KSI SPEC: AMS 6322	MIL-S-6049	B	C	U		U	U		U		U	U		
53170	STEEL 8740 FORGING <200 KSI UTS SPEC: MIL-S-6049A		B	C											
50927	STEEL 8740 FORGING >200 KSI SPEC: AMS 6322		B	C											
53168	STEEL 8740 PLATE <200 KSI UTS SPEC: AMS 6358F		B	C											
50928	STEEL 8740 RING >200 KSI SPEC: AMS 6322		B	C											
53171	STEEL 8740 RINGS <200KSI SPEC: AMS 6322K		B	C											
53166	STEEL 8740 SHEET <200 KSI UTS SPEC: AMS 6358F		B	C											
53167	STEEL 8740 STRIP <200 KSI UTS SPEC: AMS 6358F		B	C											
53172	STEEL 8740 TUBE <200 KSI UTS SPEC: AMS 6323G		B	C											
30047	STEEL 9254 SPRING Q&T		B	B	A		A	X		X		X	X		
53246	STEEL 9310 BAR ANNEALED SPEC: AMS 6260T AMS 6267B	AMS 6265F	B	C											
53247	STEEL 9310 BAR NORMALIZED		B	C											
50935	STEEL 9310 FORGING SPEC: AMS 6265		B	C											

MSFC-HDBK-527 REV F ■ 9999942 0005015 3 ■

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
30073	STEEL 9310 HOT ROLLED BAR SPEC: AMS 6265F	B	C	U	U	U		U		U	X		
50936	STEEL 9310 TUBE SPEC: AMS 6265	B	C										
53124	STEEL 98BV40 ALL 280KSI UTS	B	C										
53121	STEEL 98BV40 BAR >200KSI UTS SPEC: AMS 6423	B	C										
53122	STEEL 98BV40 FORGING >200KSI UTS SPEC: AMS 6423	B	C										
53123	STEEL 98BV40 TUBE >200KSI UTS SPEC: AMS 6423	B	C										
52684	STEEL 9NI 4CO (0.20C) PLATE 180-215 KSI UTS CVM SPEC: AMS 6523	B	C										
52672	STEEL 9NI 4CO (0.25C) ANNEALED	B	C										
52677	STEEL 9NI 4CO (0.25C) BAR 180-215 KSI UTS CVM	B	C										
52680	STEEL 9NI 4CO (0.25C) BAR ANNEALED	B	C										
52679	STEEL 9NI 4CO (0.25C) FORGING 180-215 KSI UTS SPEC: AMS 6540A	B	C										
52678	STEEL 9NI 4CO (0.25C) FORGING 180-215 KSI UTS CVM SPEC: AMS 6541A	B	C										
52669	STEEL 9NI 4CO (0.25C) PLATE 180-215 KSI UTS SPEC: AMS 6545A	B	C										
52668	STEEL 9NI 4CO (0.25C) PLATE 180-215 KSI UTS CVM SPEC: AMS 6546A	B	C										
52670	STEEL 9NI 4CO (0.25C) PLATE 235 KSI QUENCHED AND TEMPERED	B	C										
52667	STEEL 9NI 4CO (0.25C) PLATE WELDED	B	C										
52671	STEEL 9NI 4CO (0.25C) PLATE WELDED/STRESS RELIEVED	B	C										
52674	STEEL 9NI 4CO (0.25C) RINGS 180-215 KSI UTS SPEC: AMS 6540A	B	C										
52682	STEEL 9NI 4CO (0.25C) RINGS PREMIUM QUALITY CVM	B	C										
52666	STEEL 9NI 4CO (0.25C) SHEAR SPUN CASE 280-315 KSI TEMPERED	B	C										

MSFC-HDBK-527 REV F ■ 9999942 0005016 5 ■

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52675	STEEL 9NI 4CO (0.25C) SHEET 180-215 KSI UTS SPEC: AMS 6545A	B	C											
52683	STEEL 9NI 4CO (0.25C) SHEET PREMIUM QUALITY CVM SPEC: AMS 6546	B	C											
52676	STEEL 9NI 4CO (0.25C) STRIP 180-215 KSI UTS SPEC: AMS 6545A	B	C											
52673	STEEL 9NI 4CO (0.25C) TUBE 180-215 KSI UTS SPEC: AMS 6540A	B	C											
52681	STEEL 9NI 4CO (0.25C) TUBE PREMIUM QUALITY CVM	B	C											
10202	STEEL 9NI 4CO (.20C) BAR 190 KSI SPEC: MB0160-042 ST0111LA002	B	A	A		A	X		X		U	X		
50929	STEEL 9NI 4CO (.20C) FORGING 180-200 KSI SPEC: AMS 6525	B	B											
50931	STEEL 9NI 4CO (.20C) FORGING 190 KSI SPEC: MB0160-042 ST0111<A002	B	B											
50933	STEEL 9NI 4CO (.20C) PLATE 190 KSI SPEC: AMS 6523	B	B											
50930	STEEL 9NI 4CO (.20C) RING 180-200 KSI SPEC: AMS 6525	B	B											
10201	STEEL 9NI 4CO (.20C) SHEET 180-200 KSI SPEC: AMS 6523	B	B	A		A	X		X		U	X		
50932	STEEL 9NI 4CO (.20C) STRIP 190 KSI SPEC: AMS 6523	B	B											
30088	STEEL 9NI 4CO (.30C) BAR 180-200 KSI SPEC: MS19069	B	B	A		A	C		X		U	X		
50934	STEEL 9NI 4CO (.30C) FORGING 180-200 KSI SPEC: AMS 6525	B	B											
52690	STEEL 9NI 4CO (0.20C) 180-215 KSI UTS SPEC: AMS 65CD	B	A											
52685	STEEL 9NI 4CO (0.20C) ANNEALED	B	A											
52687	STEEL 9NI 4CO (0.20C) BAR 180-215 KSI UTS	B	A											
52692	STEEL 9NI 4CO (0.20C) BILLET 180-215 KSI UTS CVM	B	A											
52688	STEEL 9NI 4CO (0.20C) FORGING 180-215 KSI UTS SPEC: AMS 62CF	B	A											

MSFC-HDBK-527 REV F 9999942 0005017 7

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
52686	STEEL 9NI 4CO (0.20C) PLATE 180-215 KSI UTS SPEC: AMS 62CD AMS 6523	B	A											
52693	STEEL 9NI 4CO (0.20C) PLATE WELDED	B	A											
52695	STEEL 9NI 4CO (0.20C) QUENCHED AND TEMPERED SPEC: AMS 6523	B	A											
52694	STEEL 9NI 4CO (0.20C) ROD 180-215 KSI UTS CVM	B	A											
52691	STEEL 9NI 4CO (0.20C) STRIP 180-215 KSI UTS SPEC: AMS 65CD	B	A											
52689	STEEL 9NI 4CO (0.20C) TUBE 180-215 KSI UTS SPEC: AMS 65CD	B	A											
52696	STEEL 9NI 4CO (0.25C) STRIP PREMIUM QUALITY CVM SPEC: AMS 6546	B	C											
52637	STEEL 9NI 4CO (0.30C) BAR 220-240 KSI UTS SPEC: AMS 6526	B	A											
52632	STEEL 9NI 4CO (0.30C) PLATE 220-240 KSI UTS SPEC: AMS 6524	B	A											
52631	STEEL 9NI 4CO (0.30C) PLATE 220-240 KSI UTS CVM SPEC: AMS 65CE	B	A											
52630	STEEL 9NI 4CO (0.30C) PLATE QUENCHED AND TEMPERED SPEC: AMS 65CE	B	A											
52634	STEEL 9NI 4CO (0.30C) SHEET 220-240 KSI UTS SPEC: AMS 6524	B	A											
52628	STEEL 9NI 4CO (0.30C) SHEET QUENCHED AND TEMPERED SPEC: AMS 65CE	B	A											
52635	STEEL 9NI 4CO (0.30C) STRIP 220-240 KSI UTS SPEC: AMS 6524	B	A											
52629	STEEL 9NI 4CO (0.30C) STRIP QUENCHED AND TEMPERED SPEC: AMS 65CE	B	A											
52636	STEEL 9NI 4CO (0.30C) TUBE 220-240 KSI UTS SPEC: AMS 6526	B	A											
52650	STEEL 9NI 4CO (0.45C) ANNEALED	B	N											
52652	STEEL 9NI 4CO (0.45C) BAR 260-290 KSI UTS	B	C											
52664	STEEL 9NI 4CO (0.45C) BAR PREMIUM QUALITY CVM	B	N											

MSFC-HDBK-527 REV F 9999942 0005018 9

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZK RTG	HDZK TEMP	LOH2 RTG	LH2 RTG	LH2 PRESS	LH2 TEMP
52662	STEEL 9NI 4CO (0.45C) BILLETS AUSTEMPERED FORGING	B	N											
52651	STEEL 9NI 4CO (0.45C) FORGING 260-290 KSI UTS	B	C											
52655	STEEL 9NI 4CO (0.45C) FORGING 260-290 KSI UTS CVM SPEC: AMS 6542A	B	C											
52649	STEEL 9NI 4CO (0.45C) FORGING AUSTEMPERED	B	N											
52656	STEEL 9NI 4CO (0.45C) FORGING AUSTEMPERED CVM SPEC: AMS 6542A	B	N											
52663	STEEL 9NI 4CO (0.45C) FORGING DIE AUSTEMPERED	B	N											
52648	STEEL 9NI 4CO (0.45C) FORGING LANDING GEAR 260-290 KSI UTS	B	C											
52654	STEEL 9NI 4CO (0.45C) FORGING QUENCHED/TEMPERED CVM SPEC: AMS 6542A	B	N											
52658	STEEL 9NI 4CO (0.45C) PLATE 260-290 KSI UTS	B	C											
52661	STEEL 9NI 4CO (0.45C) PLATE 260-290 KSI UTS CVM	B	C											
52657	STEEL 9NI 4CO (0.45C) PLATE AUSTEMPERED	B	N											
52659	STEEL 9NI 4CO (0.45C) PLATE AUSTEMPERED CVM	B	N											
52660	STEEL 9NI 4CO (0.45C) PLATE QUENCHED/TEMPERED CVM	B	N											
52653	STEEL 9NI 4CO (0.45C) TUBE 260-290 KSI UTS	B	C											
52665	STEEL 9NI 4CO (0.45C) TUBE PREMIUM QUALITY CVM	B	N											
10734	STEEL 9NI 4CO BAR SPEC: AMS 6525	B	B	A		A	X		X		U	X		
52633	STEEL 9NI-4CO (.30C) ANNEALED	B	B											
50112	STEEL B1113 COLD ROLLED 180KSI	B	B	U		U	X		X		U	U		
10470	STEEL CARBON BEARING <200KSI MANF: TIMKEN	B	B	A		A	U		X		X	X		
10753	STEEL CARBON MOLYBDENUM 180-200KSI SPEC: MIL-S-12222	B	B	U		U	C		X		A	A		
10720	STEEL CARBON RC 29-33 SPEC: ASTM A36M QQ-S-741	B	A	A		A	A		X		A	A		
30089	STEEL CARPENTER 158 CARB <200 KSI	B	B	U		U	U		U		U	U		

MSFC-HDBK-527 REV F 9999942 0005019 0

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50308	STEEL CARPENTER 49 47FE 50NI		B	A	U		U	U		U		U	U		
50062	STEEL D6AC 180KSI SPEC: STW7-2608		B	B	A		A	X		X		X	X		
30109	STEEL D6AC BAR TUBE,FORGING,CVEM SPEC: AMS 6431		B	B	U		A	X		X		X	X		
50083	STEEL D6AC FORGING >180 KSI		B	C	A		A	X		X		X	X		
30110	STEEL D6AC SHEET PLATE >180 KSI SPEC: MIL-S-8949		B	B	U		A	X		X		X	X		
30076	STEEL ELEC 1.0SI CORE FE CST MANF: STERER		B	A	U		U	U		U		U	U		
30102	STEEL ELEC A-FM SI CORE IRON		B	A	U		U	U		U		U	U		
10490	STEEL ELEC M19 (3SI) SPEC: MIL-S-46084		B	A	U		U	U		X		U	U		
30092	STEEL H-11 BAR >200 KSI SPEC: AMS 6485	AMS 6487	B	C	U		U	X		X		U	U		
50850	STEEL H-11 FORGING >200 KSI SPEC: AMS 6485	AMS 6487	B	C											
10515	STEEL HIGH CARBON >200 KSI SPEC: AMS 5132 FED-STD-66	ASTM A 682	B	C	A		A	A		X		A	A		
53108	STEEL HNM BAR ANNEALED SPEC: MIL-S-17759		U	U											
53109	STEEL HNM BAR ANNEALED AND AGED SPEC: MIL-S-17759		U	U											
52640	STEEL HY-TUF BAR COLD FINISHED		B	N											
52638	STEEL HY-TUF BAR QUENCHED AND TEMPERED > 200KSI SPEC: MIL-S-7108		B	C											
52641	STEEL HY-TUF FORGING COLD FINISHED		B	N											
52639	STEEL HY-TUF FORGING QUENCHED AND TEMPERED > 200 KSI SPEC: AMS 6418		B	C											
52642	STEEL HY-TUF QUENCHED AND TEMPERED 125-145KSI		B	A											
52643	STEEL HY-TUF QUENCHED AND TEMPERED 150-170KSI		B	A											

MSFC-HDBK-527 REV F 9999942 0005020 7

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	NDMH RTG	NDMH TEMP	LOH2 RTG	MIH2 RTG	MIH2 PRESS	MIH2 TEMP
52644	STEEL HY-TUF QUENCHED AND TEMPERED 180-200KSI	B	B											
52645	STEEL HY-TUF QUENCHED AND TEMPERED 200-220KSI	B	C											
52646	STEEL HY-TUF QUENCHED AND TEMPERED 220-240KSI	B	C											
52647	STEEL HY-TUF TUBE MECHANICAL	B	N											
30130	STEEL LOW ALLOY 17-22A	B	A	A		A	X		X		X	X		
50067	STEEL M36 1.5%SI <180KSI SPEC: AMS 7711	B	A	U		U	X		X		U	U		
53103	STEEL RA-330HC ALLOY STOCK QUENCHED AND TEMPERED	A	A											
10687	STEEL SHEET LOW CARBON 180-200 KSI SPEC: QQ-S-698 QQ-S-741	B	B	A		A	X		X		A	A		
50899	STEEL SHEET LOW CARBON 180-200 KSI	B	B											
10497	STEEL SHEET PB-SN SOLDER <180 KSI	A	A	A		A	X		X		X	X		
10237	STEEL SHIM STOCK COMP 4 MILD SPEC: MIL-S-22499	B	A	A		A	A		X		X	X		
30152	STEEL SINTERE D LOW ALLOY 180-200 KSI MANF: KWIK SET K-2030F	B	B	U		U	U		U		U	U		
53252	STEEL T-1 BAR <180 KSI UTS SPEC: ASTM A514 ASTM A517	B	N											
53253	STEEL T-1 FLATS <180 KSI UTS SPEC: ASTM A514 ASTM A517	B	N											
53248	STEEL T-1 PLATE <180 KSI UTS SPEC: ASTM A514 ASTM A517	B	N											
53250	STEEL T-1 PLATE UNWELDED SPEC: ASTM A514 ASTM A517	B	N											
53249	STEEL T-1 PLATE WELDED SPEC: ASTM A514 ASTM A517	B	N											
53251	STEEL T-1 PLATE WELDED & TEMPERED SPEC: ASTM A514 ASTM A517	B	N											
53256	STEEL T-1 STRIP SPEC: ASTM A517	B	N											
53254	STEEL T-1 TUBE SEAMLESS <180 KSI UTS SPEC: ASTM A514 ASTM A517	B	N											

MSFC-HDBK-527 REV F 9999942 0005021 9

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
53255	STEEL T-1 WROUGHT <180 KSI UTS SPEC: ASTM A514		B	N										
53225	STEEL T-1A PLATE <180 KSI UTS SPEC: ASTM A514	ASTM A517	B	N										
53221	STEEL T-1A PLATE WELDED SPEC: ASTM A514	ASTM A517	B	N										
53222	STEEL T-1A PLATE WELDED & TEMPERED SPEC: ASTM A514	ASTM A517	B	N										
53223	STEEL T-1A SHEET SPEC: ASTM A514	ASTM A517	B	N										
53224	STEEL T-1A STRIP SPEC: ASTM A514	ASTM A517	B	N										
52703	STEEL T-1B PLATE SPEC: ASTM A514/A514M	ASTM A517/A517M	B	N										
10696	STEEL T-I 13V 11CR 3AL SPRING WIRE SPEC: AMS 4959	LB0170-194	A	A	X	A	A		A		X	X		
30098	STEEL TOOL 01 RC24-27 SPEC: MAS 5643		B	A	A	A	U		X		X	X		
10699	STEEL TOOL CARBON VANAD <200KSI SPEC: ASTM A686	QQ-T-580	B	C	A	A	U		X		X	X		
30040	STEEL TOOL D2 RC 58-62 BARS SPEC: ASTM A600	QQ-T-570	B	C	A	A	U		X		X	X		
50900	STEEL TOOL FORGING M50 RC58-64 SPEC: AMS 6490		B	C										
30039	STEEL TOOL M2 RC 32-48 BARS SPEC: ASTM A600	QQ-T-590	B	C	A	A	U		A		X	X		
52743	STEEL TOOL M50 BAR SPHEROIDIZE ANNEALED		B	N	A	A	U		X		X	X		
52745	STEEL TOOL M50 FORGING ANNEALED CVM SPEC: AMS 6491		B	N	A	A	U		X		X	X		
30038	STEEL TOOL M50 RC58-64 BAR SPEC: AMS 6490		B	C	A	A	U		X		X	X		
52746	STEEL TOOL M50 TUBE		B	N	A	A	U		X		X	X		
52744	STEEL TOOL M50 TUBE SPHEROIDIZE ANNEALED MECHANICAL SPEC: AMS 6491		B	N	A	A	U		X		X	X		

MSFC-HDBK-527 REV F 9999942 0005022 0

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50180	STEEL VASCO MATRIX		B	U	A		A	U		U		U	U		
10499	STEEL WIRE COPPER/CLAD <180KSI		A	A	U		A	U		X		X	X		
10232	STEEL WIRE SPRING MUSIC SPEC: QQ-W-470		B	A	A		A	U		X		X	X		
10468	STOODY NO. 2 >200KSI		A	U	A		A	A		X		A	A		
10679	STOODY NO. 6 MANF: STOODY CO		A	U	A		A	A		A		A	A		
10682	T/C ALLOY 50% RHENIUM MANF: SIMMONDS PREC		A	N	U		A	A		C		U	U		
10666	T/C ALLOY CHROMEL-ALUMEL WIRE SPEC: MIL-W-5846		A	N	A		A	A		X		A	X		
10725	T/C ALLOY COPPER TY RH SPEC: ANSIC96.1-1964		A	N	A		A	X		X		A	A		
10668	T/C ALLOY PLATINUM TY RH WIRE SPEC: ANSI-C96 1-1964		A	N	U		U	U		U		U	U		
10665	T/C ALLOY PLATINUM/PT-RH SPEC: ASTM E 230		A	N	U		U	U		U		U	U		
10692	T/C ALLOY W-5 RHEN/W-26 RHEN		A	N	U		U	U		U		U	U		
10691	TANTALUM		A	A	U		U	U		U		U	U		
10496	TIN SPEC: QQ-T-276		A	A	X		X	A		X		C	C		
30144	TITANIUM 13V-11CR-3Al SPEC: AMS 4959		A	A	X		X	A		A		X	X		
10310	TITANIUM 3AL 2.5V FOIL ANNEALED SPEC: MB0170-101	MB0170-100	A	A	X		X	A		A		X	X		
10061	TITANIUM 3AL 2.5V TUBE SPEC: MB0170-084		A	A	X		X	A		A		X	X		
10453	TITANIUM 3AL 2.5V TUBE ANNEALED SPEC: AMS 4943	MB0170-097	A	A	X		X	A		A		X	X		
10712	TITANIUM 45%CB BAR ANNEALED SPEC: AMS 4982		A	A	X		X	U		U		X	X		
50247	TITANIUM 4AL 4MO 2SN .5SI BAR		A	A	X		X	A		X		A	U		

MSFC-HDBK-527 REV F 9999942 0005023 2

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10059	TITANIUM 5AL 2.5SN BAR EXTRUDED ANNEALED SPEC: MIL-T-81556	A	A	X		X	A		A		X	X		
10058	TITANIUM 5AL 2.5SN BAR FORGING ANNEALED SPEC: MIL-T-9047	A	A	X		X	A		A		X	X		
10060	TITANIUM 5AL 2.5SN BAR FORGING ANNEALED ELI SPEC: MIL-F-83142 MIL-T-9047	A	A	X		X	A		A		X	X		
10057	TITANIUM 5AL 2.5SN PLATE ANNEALED SPEC: MIL-T-9046	A	A	X		A	A		A		X	X		
50944	TITANIUM 5AL 2.5SN ROD EXTRUDED ANNEALED SPEC: MIL-T-81556	A	A	X		A	A		A		X	X		
50946	TITANIUM 5AL 2.5SN SHEET ANNEALED SPEC: MIL-T-9046	A	A	A		A	A		A		X	X		
50945	TITANIUM 5AL 2.5SN STRIP ANNEALED SPEC: MIL-T-9046	A	A	X		A	A		A		X	X		
10069	TITANIUM 6AL 4V BAR SPEC: MB0170-081S C2 MB0170-089S MIL-T-9047	A	A	X		X	A		A		X	X		
10365	TITANIUM 6AL 4V BAR 120 KSI SPEC: AMS 4928 AMS 4967	A	A	X		X	A		A		X	X		
10438	TITANIUM 6AL 4V BAR ANNEALED 125KSI ELI SPEC: MIL-T-9047	A	A	X		X	A		A		X	X		
10402	TITANIUM 6AL 4V BAR ANNEALED STA SPEC: AMS 4967	A	A	X		X	A		A		X	X		
10398	TITANIUM 6AL 4V BAR DIFFUSION BOND SPEC: MB0170-081 MB0170-082	A	A	X		X	A		A		X	X		
10070	TITANIUM 6AL 4V BAR EXTRUDED STA SPEC: MIL-T-81556	A	A	X		X	A		A		X	X		
10066	TITANIUM 6AL 4V BAR HI-QUAL 55KSI SPEC: MB0170-081 CL 2 MB0170-089 S MIL-T-9047	A	A	X		X	A		A		X	X		
10067	TITANIUM 6AL 4V BAR ROD EXTRUDED ANNEALED SPEC: MIL-T-81556	A	A	X		X	A		A		X	X		
10401	TITANIUM 6AL 4V BAR STA SPEC: AMS 4965	A	A	X		X	A		A		X	X		
50182	TITANIUM 6AL 4V CASTING ANNEALED	A	A	X		X	A		A		X	X		

MSFC-HDBK-527 REV F 9999942 0005024 4

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	NH2 RTG	NH2 PRESS	NH2 TEMP
10729	TITANIUM 6AL 4V CASTING INVESTMENT 180-200KSI SPEC: MIL-T-81915		A	A	X		X	A		A		X	X		
10369	TITANIUM 6AL 4V FORGING ANNEALED SPEC: MIL-F-83142 CP6		A	A	X		X	A		A		X	X		
10032	TITANIUM 6AL 4V FORGING HI-QUAL SPEC: MB0170-081	MB0170-089	A	A	X		X	A		A		X	X		
50953	TITANIUM 6AL 4V FORGING STA SPEC: AMS 4965		X	X				A		A		X	X		
10383	TITANIUM 6AL 4V FORGING STOCK SPEC: MIL-T-9047		A	A	X		X	A		A		X	X		
50951	TITANIUM 6AL 4V PLATE SPEC: MB0170-082S	MIL-T-9046	X	X				A		A		X	X		
50949	TITANIUM 6AL 4V PLATE ANNEALED SPEC: AMS 4911	MIL-T-9046	A	A	X		X	A		A		X	X		
10034	TITANIUM 6AL 4V PLATE DIFFUSION BOND SPEC: MB0170-082		A	A	X		X	A		A		X	X		
50952	TITANIUM 6AL 4V ROD ANNEALED SPEC: AMS 4967		A	A	X		X	A		A		X	X		
50947	TITANIUM 6AL 4V ROD EXTRUDED ANNEALED SPEC: MIL-T-81556		A	A	X		X	A		A		A	A		
50954	TITANIUM 6AL 4V ROD EXTRUDED STA SPEC: MIL-T-81556		A	A	X		X	A		A		X	X		
10068	TITANIUM 6AL 4V SHEET SPEC: MB0170-082S	MIL-T-9046	A	A	X		X	A		A		X	X		
10065	TITANIUM 6AL 4V SHEET ANNEALED SPEC: AMS 4911 MIL-T-9046	MB0170-082S	A	A	X		X	A		A		X	X		
50950	TITANIUM 6AL 4V STRIP SPEC: MIL-T-9046		A	A	X		X	A		A		X	X		
50948	TITANIUM 6AL 4V STRIP ANNEALED SPEC: AMS 4911	MIL-T-9046	A	A	X		X	A		A		X	X		
10295	TITANIUM 6AL 6V 2SN BAR ANNEALED SPEC: MIL-T-9047		A	A	X		X	A		A		X	X		
10414	TITANIUM 6AL 6V 2SN EXTRUSION SPEC: MIL-T-81556		A	A	X		X	A		A		X	X		

MSFC-HDBK-527 REV F ■ 9999942 0005025 6 ■

Information Handling Services, 2000

		COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
50955	TITANIUM 6AL 6V 2SN FORGING ANNEALED SPEC: MIL-T-9047	A	A	X		X	A		A		X	X		
50956	TITANIUM 6AL 6V 2SN PLATE ANNEALED SPEC: MIL-T-9046	A	A	X		X	A		A		X	X		
10072	TITANIUM 6AL 6V 2SN SHEET ANNEALED SPEC: MIL-T-9046	A	A	X		X	A		A		X	X		
50957	TITANIUM 6AL 6V 2SN STRIP ANNEALED SPEC: MIL-T-9046	A	A	A		A	A		A		X	X		
10056	TITANIUM COMM PURE BAR 55KSI SPEC: MIL-T-81556	A	A	X		X	A		A		X	X		
10055	TITANIUM COMM PURE BAR ANNEALED 55KSI SPEC: ASTM B348 GR3 MIL-T-9047	A	A	X		X	A		A		X	X		
10444	TITANIUM COMM PURE BAR ANNEALED 70 KSI SPEC: AMS 4921	A	A	X		X	A		A		X	X		
50937	TITANIUM COMM PURE FORGING ANNEALED 70 KSI SPEC: AMS 4921	A	A	X		X	A		A		X	X		
50941	TITANIUM COMM PURE PLATE ANNEALED 55 KSI SPEC: AMS 4900 MIL-T-9046	A	A	X		X	A		A		X	X		
50938	TITANIUM COMM PURE RINGS ANNEALED 70 KSI SPEC: AMS 4921	A	A	X		X	A		A		X	X		
50942	TITANIUM COMM PURE ROD 55KSI SPEC: MIL-T-81556	A	A	X		X	A		A		X	X		
50943	TITANIUM COMM PURE SHAPES 55KSI SPEC: MIL-T-81556	A	A	X		X	A		A		X	X		
10054	TITANIUM COMM PURE SHEET ANNEALED 55KSI SPEC: AMS 4900 MIL-T-9046	A	A	X		X	A		A		X	X		
50940	TITANIUM COMM PURE STRIP ANNEALED 55 KSI SPEC: AMS 4900 MIL-T-9046	A	A	X		X	A		A		X	X		
10298	TITANIUM COMM PURE TUBE ANNEALED <55KSI SPEC: ASTM B338	A	A	X		X	A		A		X	X		
30151	TUNGSTEN KENNERTIUM W-2	B	A	U		U	X		X		U	U		
30107	TUNGSTEN MALLORY ALLOY 2000 SPEC: AMS 7725	A	A	U		U	U		U		U	U		
30050	TUNGSTEN SUPERDENSALLOY 180 MANF: PWDER ALLOY-TELEDYNE SPEC: MIL-T-21014	A	A	U		U	X		X		U	U		

MSFC-HDBK-527 REV F ■ 9999942 0005026 8 ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDIE RTG	HDIE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10522	VELCRO (304/INCO-750/ELGILOY) MANF: VELCRO CORP SPEC: MB0160-048		A	A	A		A	A		A		C	X		
30125	WASPALOY BAR FORGING SPEC: AMS 5708		A	A	U		U	U		U		U	U		
50243	WELD ELECTRODE 20CU 80AL CUPAL MANF: ELECTROLOY		B	B	A		A	A		X		A	A		
10165	WELD WIRE 5AL 2.5SN UNCOATED SPEC: MB0170-073		A	N	X	1000	A	X		A		X	X		
50074	WELD WIRE AL 2319 MANF: SIGMUND COHN CORP SPEC: MIL-E-16053	QQ-R-566	B	N	A		A	A		A		U	U		
10185	WELD WIRE AL 4043 UNCOATED SPEC: MB0170-073	QQ-R-566 CL 1	B	N	X		U	A		A		A	A		
10162	WELD WIRE AL 5356 UNCOATED SPEC: MB0170-073		B	N	A		A	A		A		A	A		
10163	WELD WIRE AL 5556 UNCOATED SPEC: MB0170-073		B	N	A		A	A		A		A	A		
50215	WELD WIRE AL 5754		U	N	U		U	U		U		U	U		
10194	WELD WIRE CO BASE HAYNES 188 SPEC: AMS 5801	MB0170-073	A	N	A		A	A		X		A	A		
10195	WELD WIRE CO BASE HAYNES 25 SPEC: MB0170-073		A	N	A		A	A		X		A	A		
10229	WELD WIRE CRES 13-7 MO ELEC SPEC: MB0170-073		A	N	A		A	A		A		A	X		
10173	WELD WIRE CRES 13PH-8 SPEC: MB0170-073		A	N	A		A	A		A		A	X		
10172	WELD WIRE CRES 14PH-8 SPEC: MB0170-073		A	N	A		A	A		A		A	X		
10170	WELD WIRE CRES 17-4PH SPEC: MB0170-073		A	N	A	3300	A	A		A		A	X		
10181	WELD WIRE CRES 21-6-9 SPEC: MB0170-073		A	N	A		A	A		A		A	A		
10655	WELD WIRE CRES 29-9 SPEC: AMS 5784		A	N	A		A	X		X		A	A		

MSFC-HDBK-527 REV F ■ 9999942 0005027 T ■

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10175	WELD WIRE CRES 308 ELEC SPEC: MB0170-073		A	N	A	3300	A	A		A		A	A		
10177	WELD WIRE CRES 310 UNCOATED SPEC: MB0170-073		A	N	A	1300	A	X		U		A	A		
10179	WELD WIRE CRES 316 ELC SPEC: MB0170-073		A	N	A	1300	A	A		A		A	A		
10178	WELD WIRE CRES 316 UNCOATED SPEC: MB0170-073		A	N	A	1300	A	A		A		A	A		
10180	WELD WIRE CRES 321 UNCOATED SPEC: MB0170-073		A	N	A	3300	A	A		A		A	A		
10176	WELD WIRE CRES 347 SPEC: MB0170-073 UNC	MIL-E-22200/2 C	A	N	A	3300	A	A		A		A	A		
10323	WELD WIRE CRES 349 SPEC: AMS 5782	MIL-R-5031 CL6	A	N	A		A	A		A		A	A		
10230	WELD WIRE CRES A286 UNCOATED SPEC: MB0170-073		A	N	A	3000	A	A		A		A	A		
10174	WELD WIRE CRES AM350 UNCOATED SPEC: MB0170-073		A	N	A		A	X		X		A	U		
10228	WELD WIRE CRES AM355 UNCOATED SPEC: MB0170-073		A	N	A		A	U		U		A	U		
10168	WELD WIRE ELI TI 5AL 2.5SN SPEC: MB0170-073		A	N	X	1000	A	X		A		X	X		
10169	WELD WIRE ELI TI 6AL 4V SPEC: AMS 4956	MB0170-073	A	N	X	1000	A	X		A		X	X		
10167	WELD WIRE ELI TI CP UNCOATED SPEC: MB0170-073		A	N	X	1000	A	X		A		X	X		
50198	WELD WIRE INCO 88 42NI 32FE 20CR		U	N	U		U	U		U		U	U		
50192	WELD WIRE INCOLOY 903		A	N	A		A	X		X		A	A		
50191	WELD WIRE INCONEL 61		U	N	U		U	U		U		U	X		
10700	WELD WIRE NI + CO SPEC: MIL-STD-1276		A	N	A		A	A		X		U	X		
10188	WELD WIRE NI BASE HASTELLOY W SPEC: AMS 5786 MIL-R-5031/12	MB0170-073	A	N	A	1000	A	A		A		U	X		

MSFC-HDBK-527 REV F 9999942 0005028 1

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10190	WELD WIRE NI BASE INCO 62 SPEC: AMS 5679	MB0170-073	A	N	A	4500	A	X		X		C	X		
10193	WELD WIRE NI BASE INCO 625 SPEC: AMS 5837	MB0170-073	A	N	A	1600	A	X		X		C	X		
10191	WELD WIRE NI BASE INCO 69 SPEC: MB0170-073		A	N	A	4500	A	X		X		C	X		
10189	WELD WIRE NI BASE INCO 718 SPEC: AMS 5832	MB0170-073	A	N	A	4500	A	A		A		A	X		
10192	WELD WIRE NI BASE INCO 82 SPEC: MB0170-073	MIL-E-21562	A	N	A	1600	A	X		X		C	X		
50137	WELD WIRE NI-CU BASE SPEC: AWS A5.14-76		A	N	U		U	U		U		U	U		
10184	WELD WIRE STEEL 17-22AS SPEC: MB0170-073		B	N	A		A	X		X		X	X		
10187	WELD WIRE STEEL 18-7 MAR SPEC: MB0170-073		B	N	A		A	X		X		A	X		
10186	WELD WIRE STEEL 9NI 4CO 2C SPEC: MB0170-073		B	N	A		A	X		X		U	X		
10357	WELD WIRE STEEL AWS E 705-2 SPEC: MIL-E-23765		B	N	U		U	U		U		U	U		
10730	WELD WIRE STEEL E10018 SPEC: AWS A5.5		B	N	A		A	X		X		X	X		
10182	WELD WIRE STEEL ER 502 SPEC: MB0170-073		B	N	A		A	X		X		X	X		
10183	WELD WIRE STEEL OXWELD 71 SPEC: MB0170-073		B	N	A		A	X		X		X	X		
10739	WELD WIRE TI 6AL 4V SPEC: AMS 4954		A	N	X		A	A		A		X	X		
10166	WELD WIRE TI 6AL 4V ELI BAR SPEC: AMS 4956	MB0170-073	A	N	X		A	X		A		X	X		
10164	WELD WIRE TI CP UNCOATED SPEC: MB0170-073		A	N	X	1000	A	X		A		X	X		
10609	WIRE 479 92PT8W RESISTANCE MANF: SIGMUND COHN CORP		A	A	U		U	U		U		U	U		

Information Handling Services, 2000

			COR RTG	SCC RTG	GOX RTG	GOX PRESS	LOX RTG	N2O4 RTG	N2O4 TEMP	HDZE RTG	HDZE TEMP	LOH2 RTG	HIH2 RTG	HIH2 PRESS	HIH2 TEMP
10680	WIRE 60NI-16CR-24FE ELECTRICAL SPEC: QQ-R-175 COMP D		A	A	A		A	A		A		C	X		
10663	WIRE 75NI 20CR RESIST EVANOPHM SPEC: AMS 5682	ASTM B 344	A	A	U		U	U		U		U	U		
10662	WIRE 88CU 12NI		A	A	U		U	U		U		U	U		
10231	WIRE ALLOY X750 #1 TEMPER SPEC: AMS 5698		A	A	A	3300	A	A		A		A	X		
10150	WIRE ALLOY X750 SPRING TEMPER SPEC: AMS 5699		A	A	A	3300	A	X		C		A	X		
10678	WIRE COPPER STEEL CLAD SPEC: ASTM B 227		A	A	A		A	X		X		U	U		
10330	WIRE COPPER TIN PLATED SPEC: ASTM B-172 QQ-B-575	MIL-W-16878/8 QQ-W-343 TYPE S	A	N	A		A	A		X		C	C		
30192	WIRE COPPER-NICKEL-MANGANESE		A	A	A		A	A		X		U	X		
10733	WIRE CU AG COATED CLAD SPEC: ASTM B501		A	A	A		A	X		X		X	X		
10223	WIRE CU,NI COATED ELECTRICAL SPEC: ASTM B355		A	A	A	1600	A	A		X		U	X		
10658	WIRE NICHROME V COATING ALLOY SPEC: 78NI 20CR ASTM B 344	AMS 5682	A	A	A		A	X		X		C	X		
10677	WIRE NICHROME-TOPHET C RESIST MANF: THERMATICS INC		A	A	U		U	U		U		U	U		

MSFC-HDBK-527 REV F 9999942 0005030 T

Information Handling Services, 2000

TABLE 1B

METALS BY SPECIFICATION

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
	COPPER 100% STRIP ANNEALED	50838
78NI 20CR	WIRE NICHROME V COATING ALLOY	10658
ALCOA 23F	BRAZE AL ALLOY 10SI 1.2MN	10721
ALCOA 5652	AL 5652-O SHEET	30188
ALCOA 718	BRAZE AL ALLOY 4047	10440
AMS 2400	PLATING CADMIUM ELECTRODEPOSIT	30082
	PLATING CADMIUM	50124
AMS 2403	PLATING NICKEL ELECTRODEPOSIT	10308
AMS 2404	PLATING NICKEL ELECTROLESS	10046
AMS 2408	PLATING TIN	10312
AMS 2411	PLATING SILVER FASTENERS ONLY	10281
AMS 2418	PLATING COPPER ELECTRODEPOSIT	10311
AMS 2437	COATING PLASMA SPRAY DEPOSITED	10717
AMS 2488	COATING ANODIC TIODIZE	10649
AMS 4001	AL 1100-O SHEET	10279
	AL 1100-O PLATE	50534
AMS 4003	AL 1100-H14 PLATE	50974
	AL 1100-H14 SHEET	50975
AMS 4004	AL 5052-H191 FOIL	10033
AMS 4006	AL 3003-O SHEET	10282
	AL 3003-O PLATE	50600
AMS 4008	AL 3003-H14 SHEET	52963
	AL 3003-H14 PLATE	52964
AMS 4009	AL 6061-O FOIL	51287
AMS 4010	AL 3003 FOIL	50601
AMS 4014	AL 2014-T651 PLATE	51514
AMS 4015	AL 5052-O SHEET	50216
	AL 5052-O PLATE	50611
AMS 4016	AL 5052-H32 SHEET	10112
	AL 5052-H32 PLATE	50607
AMS 4017	AL 5052-H34 SHEET	50271
	AL 5052-H34 PLATE	50608
AMS 4025	AL 6061 SHEET ANNEALED	10325
	AL 6061 PLATE ANNEALED	50631
	AL 6061-T6 PLATE	50645
AMS 4025G	AL 6061-O SHEET	50148
	AL 6061-O PLATE	50654
AMS 4026	AL 6061-T4 SHEET	10018
	AL 6061-T4 PLATE	50642
AMS 4027	AL 6061-T6 SHEET	10022
	AL 6061-T6 PLATE	50645
AMS 4028	AL 2014-O SHEET	51504
	AL 2014-O PLATE	51510
AMS 4029	AL 2014-T6 SHEET	51508
AMS 4031	AL 2219-O SHEET	51046
	AL 2219-O PLATE	51047
AMS 4035	AL 2024-O SHEET	30140
	AL 2024-O PLATE	51090
AMS 4036	AL 2024-T3 SHEET ONE SIDE CLAD	52881
	AL 2024-T351 PLATE ONE SIDE CLAD	52882
AMS 4037	AL 2024-T3 SHEET	30111
	AL 2024-T351 PLATE	50558
	AL 2024-T4 PLATE	50564
AMS 4039	AL 7075-T651 PLATE CLAD	52434
	AL 7075-T651 PLATE CLAD	52435
AMS 4040	AL 2024-O PLATE CLAD	10408
	AL 2024-O SHEET CLAD	50581
AMS 4041	AL 2024-T3 SHEET CLAD	50256
	AL 2024-T351 PLATE CLAD	50557
AMS 4044	AL 7075-O SHEET	51378
	AL 7075-O PLATE	51379
AMS 4045	AL 7075-T6 SHEET	10028
	AL 7075-T651 PLATE	51382
AMS 4046	AL 7075-T6 SHEET ONE SIDE CLAD	52449
	AL 7075-T6 PLATE ONE SIDE CLAD	52454
AMS 4048	AL 7075-O SHEET CLAD	52430
	AL 7075-O PLATE CLAD	52432
AMS 4049	AL 7075-T6 SHEET CLAD	10457
	AL 7075-T6 PLATE CLAD	52436
AMS 4050	AL 7050-T7451 PLATE	52288
AMS 4051	AL 7178-O SHEET CLAD	52475
	AL 7178-O PLATE CLAD	52476
AMS 4054	BRAZE AL#21-O SHEET (CL ONE SIDE	30186
AMS 4055	BRAZE AL#22-O SHEET 2-SIDES CLAD	30185
AMS 4056D	AL 5083-O SHEET	51232
	AL 5083-O PLATE	51236
AMS 4057D	AL 5083-H323 SHEET	51234
AMS 4058D	AL 5083-H343 SHEET	51235
AMS 4059E	AL 5083-H321 SHEET	51233
	AL 5083-H321 PLATE	51237
AMS 4062	AL 1100-H14 TUBE DRAWN	51986
	AL 1100-H14 TUBE DRAWN SEAMLESS	51990
AMS 4063	AL 3003 1-SIDE CLAD W/AL 4343	10659
AMS 4064	AL 3003 CLAD W/AL 4343	50368
AMS 4065	AL 3003-O TUBE DRAWN SEAMLESS	53002
AMS 4067	AL 3003-H14 TUBE DRAWN SEAMLESS	53004
AMS 4069	AL 5052-O TUBE DRAWN SEAMLESS SPECIAL TO	52800
AMS 4070	AL 5052-O TUBE DRAWN SEAMLESS	52795
AMS 4071	AL 5052-O TUBE DRAWN SEAMLESS HYDRAULIC	52801
AMS 4077	AL 2024-O SHEET ONE SIDE CLAD	52883
	AL 2024-O PLATE ONE SIDE CLAD	52884
AMS 4078	AL 7075-T7351 PLATE	50669
AMS 4080	AL 6061-O TUBE DRAWN	51261
AMS 4082	AL 6061-T6 TUBE DRAWN	51263
AMS 4084	AL 7475-T61 SHEET	51562
AMS 4085	AL 7475-T761 SHEET	51563
AMS 4086	AL 2024-T3 TUBE DRAWN SEAMLESS	50554
	AL 2024-T3 TUBE HYDRAULIC	53036
AMS 4087	AL 2024-T42 SHEET CLAD	50259
	AL 2024-O TUBE DRAWN SEAMLESS	51127
	AL 2024-O TUBE DRAWN	53030
AMS 4088	AL 2024-T3 TUBE DRAWN SEAMLESS	50554
	AL 2024-T3 TUBE DRAWN	53035
AMS 4089	AL 7475-T7651 PLATE	51565
AMS 4090	AL 7475-T651 PLATE	51564
AMS 4096	AL 2219-O PLATE CLAD	53083
AMS 4101	AL 2124-T851 PLATE	10006
AMS 4102	AL 1100-F WIRE ROLLED	51972
	AL 1100-F ROD ROLLED	51973
	AL 1100-F BAR ROLLED	51974

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
AMS 4102	AL 1100-F WIRE COLD FINISHED	52583
	AL 1100-F ROD COLD FINISHED	52584
	AL 1100-F BAR COLD FINISHED	52585
AMS 4107	AL 7050-T74 FORGING DIE	52299
AMS 4108	AL 7050-T7452 FORGING HAND	52298
AMS 4110	AL 2017-T451 BAR ROLLED	50253
	AL 2017-T451 ROD ROLLED	50547
AMS 4111	AL 7049-T73 FORGING	10026
AMS 4112	AL 2024-T6 ROD ROLLED	10292
	AL 2024-T6 BAR COLD FINISHED	50221
	AL 2024-T6 WIRE COLD FINISHED	50566
	AL 2024-T6 BAR ROLLED	51098
	AL 2024-T6 ROD COLD FINISHED	53053
	AL 2024-T6 WIRE ROLLED	53054
AMS 4113	AL 6061-T6 SHAPES STANDARD STRUCTURAL	51283
AMS 4114	AL 5052-F ROD ROLLED	51918
	AL 5052-F BAR ROLLED	51919
	AL 5052-F WIRE ROLLED	51920
	AL 5052-F ROD COLD FINISHED	52792
	AL 5052-F BAR COLD FINISHED	52793
	AL 5082-F WIRE COLD FINISHED	52794
	AL 5052-F WIRE COLD FINISHED	53076
AMS 4115	AL 6061 BAR ANNEALED	10670
AMS 4115D	AL 6061-O BAR ROLLED	50269
	AL 6061-O ROD DRAWN	50632
	AL 6061-O ROD ROLLED	50652
AMS 4116	AL 6061-T4 WIRE COLD FINISHED	50633
	AL 6061-T4 ROD ROLLED	50640
	AL 6061-T4 SHAPES ROLLED	50641
	AL 6061-T4 WIRE ROLLED	51308
AMS 4116D	AL 6061-T4 BAR ROLLED	10019
AMS 4117	AL 6061-T6 BAR ROLLED	10023
	AL 6061-T6 SHAPE ROLLED	50650
	AL 6061-T6 ROD ROLLED	50651
	AL 6061-T6 BAR DRAWN	51296
	AL 6061-T6 BAR COLD FINISHED	51298
	AL 6061-T6 ROD DRAWN	51302
	AL 6061-T6 ROD COLD FINISHED	51305
	AL 6061-T6 WIRE ROLLED	51310
	AL 6061-T6 WIRE DRAWN	51314
AMS 4118	AL 2017-T4 BAR ROLLED	50255
	AL 2017-T4 ROD ROLLED	50543
	AL 2017-T4 WIRE ROLLED	50544
AMS 4119	AL 2024-T351 BAR ROLLED	51106
	AL 2024-T351 ROD ROLLED	51107
	AL 2024-T351 BAR COLD FINISHED	53037
	AL 2024-T351 ROD COLD FINISHED	53038
AMS 4120	AL 2024-T4 BAR ROLLED	50267
	AL 2024-T4 ROD ROLLED	50560
	AL 2024-T4 BAR COLD FINISHED	53046
	AL 2024-T4 ROD COLD FINISHED	53047
AMS 4121	AL 2014-T6 BAR COLD FINISHED	50220
	AL 2014-T6 ROD ROLLED	52310
	AL 2014-T6 ROD COLD FINISHED	52317
	AL 2014-T6 WIRE ROLLED	52324
AMS 4121	AL 2014-T6 WIRE COLD FINISHED	52331
	AL 2014-T6 BAR DRAWN	52338
	AL 2014-T6 ROD DRAWN	52345
	AL 2014-T6 WIRE DRAWN	52349
	AL 2014-T6 BAR ROLLED	53028
AMS 4122	AL 7075-T6 WIRE ROLLED	51387
	AL 7075-T6 ROD ROLLED	51389
	AL 7075-T6 BAR ROLLED	51391
AMS 4123	AL 7075-T651 ROD ROLLED	51401
	AL 7075-T651 ROD COLD FINISHED	51402
	AL 7075-T651 BAR ROLLED	51403
	AL 7075-T651 BAR COLD FINISHED	51404
AMS 4124	AL 7075-T7351 BAR ROLLED	10047
	AL 7075-T7351 BAR COLD FINISHED	51415
AMS 4125	AL 6151-T6 FORGING DIE	50989
AMS 4126	AL 7075-T6 FORGING	50101
	AL 7075-T6 FORGING DIE	52928
AMS 4127	AL 6061-F FORGING STOCK	51284
	AL 6061-T6 FORGING DIE	51359
	AL 6061-T6 RINGS ROLLED	51363
AMS 4129	AL 6061-T651 BAR COLD FINISHED	51299
	AL 6061-T651 ROD COLD FINISHED	51307
AMS 4130	AL 2025-F FORGING DIE	51140
	AL 2025-F FORGING STOCK	51142
	AL 2025-T6 FORGING	52619
AMS 4131	AL 7075-T736 FORGING	51494
AMS 4132C	AL 2618-T61 FORGING DIE	51146
	AL 2618-T61 FORGING HAND	51147
	AL 2618-T61 FORGING STOCK	51166
	AL 2618-T61 ROLLED RINGS	53025
AMS 4133	AL 2014-T6 FORGING	52420
	AL 2014 FORGING STOCK	52421
AMS 4134	AL 2014-T4 FORGING	52422
AMS 4135	AL 2014-T6 FORGING	52420
AMS 4140	AL 2018-T61 FORGING DIE	51593
AMS 4141	AL 7075-T73 FORGING DIE	51485
	AL 7075-T73 FORGING STOCK	51493
AMS 4142	AL 2218-F FORGING DIE	51190
AMS 4143	AL 2219-T6 FORGING HAND	10014
	AL 2219-T6 FORGING DIE	50590
AMS 4144	AL 2219-T852 FORGING HAND	10007
AMS 4146	AL 6061-F FORGING STOCK	51284
	AL 6061-T4 FORGING DIE	51285
	AL 6061-T4 RINGS ROLLED	51286
AMS 4147	AL 7075-T7352 FORGING	10048
	AL 7075-T7352 FORGING DIE	52929
AMS 4148	AL 7175-T66 FORGING DIE	51542
AMS 4149	AL 7175-T74 FORGING DIE	51543
	AL 7175-T74 FORGING HAND	51544
AMS 4150	AL 6061-T6 BAR EXTRUDED	10024
	AL 6061-T6 ROD EXTRUDED	50643
	AL 6061-T6 WIRE EXTRUDED	50644
	AL 6061-T6 SHAPES EXTRUDED	51332
	AL 6061-T6 TUBE EXTRUDED	51349
AMS 4152	AL 2024-T4 BAR EXTRUDED	51116

MSFC-HDBK-527 REV F 9999942 0005033 5

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
AMS 4152	AL 2024-T4 TUBE EXTRUDED	51126
	AL 2024-T4 ROD EXTRUDED	51154
	AL 2024-T4 SHAPES EXTRUDED	51161
AMS 4153	AL 2014-T6 BAR EXTRUDED	52360
	AL 2014-T6 ROD EXTRUDED	52369
	AL 2014-T6 SHAPES EXTRUDED	52378
	AL 2014-T6 TUBE EXTRUDED	52387
AMS 4154	AL 7075-T6 WIRE EXTRUDED	51459
	AL 7075-T6 ROD EXTRUDED	51460
	AL 7075-T6 BAR EXTRUDED	51461
	AL 7075-T6 SHAPES EXTRUDED	51462
	AL 7075-T6 TUBE EXTRUDED	51463
AMS 4156	AL 6063-T6 BAR EXTRUDED	50970
	AL 6063-T6 WIRE EXTRUDED	52140
	AL 6063-T6 ROD EXTRUDED	52141
	AL 6063-T6 SHAPES EXTRUDED	52143
	AL 6063-T6 TUBE EXTRUDED	52145
AMS 4157	AL 7049-T73510 EXTRUSIONS	51789
	AL 7049-T73511 EXTRUSIONS	51790
AMS 4159	AL 7049-T76510 EXTRUSIONS	51791
	AL 7049-T76511 EXTRUSIONS	51792
AMS 4160	AL 6061 BAR ANNEALED	10670
AMS 4160D	AL 6061-O WIRE EXTRUDED	50653
	AL 6061-O SHAPES EXTRUDED	51331
	AL 6061-O TUBE EXTRUDED	51341
AMS 4161	AL 6061-T4 TUBE	10732
	AL 6061-T4 WIRE EXTRUDED	51352
AMS 4162	AL 2219-T8511 BAR EXTRUDED	10013
	AL 2219-T8511 ROD EXTRUDED	50593
	AL 2219-T8511 SHAPES EXTRUDED	50594
	AL 2219-T8511 TUBE EXTRUDED	51079
AMS 4163	AL 2219-T3511 BAR EXTRUDED	50088
	AL 2219-T3511 ROD EXTRUDED	50585
	AL 2219-T3511 SHAPES EXTRUDED	51066
	AL 2219-T3511 TUBE EXTRUDED	51067
AMS 4164	AL 2024-T3510 BAR EXTRUDED	51113
	AL 2024-T3510 TUBE EXTRUDED	51120
	AL 2024-T3510 ROD EXTRUDED	51150
	AL 2024-T3510 SHAPES EXTRUDED	51157
	AL 2024-T3510 TUBE ROUND EXTRUDED	53039
AMS 4165	AL 2024-T3511 BAR EXTRUDED	51114
	AL 2024-T3511 TUBE EXTRUDED	51121
	AL 2024-T3511 ROD EXTRUDED	51151
	AL 2024-T3511 SHAPES EXTRUDED	51158
	AL 2024-T3511 TUBE ROUND EXTRUDED	53043
AMS 4166	AL 7075-T73 TUBE EXTRUDED	50509
	AL 7075-T73 WIRE EXTRUDED	51431
	AL 7075-T73 ROD EXTRUDED	51432
	AL 7075-T73 BAR EXTRUDED	51433
	AL 7075-T73 SHAPES EXTRUDED	51434
AMS 4167	AL 7075-T73511 BAR EXTRUDED	10421
	AL 7075-T73511 ROD EXTRUDED	50666
	AL 7075-T73511 WIRE EXTRUDED	50667
	AL 7075-T73511 SHAPES EXTRUDED	51440
AMS 4168	AL 7075-T6510 WIRE EXTRUDED	51467
AMS 4168	AL 7075-T6510 ROD EXTRUDED	51468
	AL 7075-T6510 BAR EXTRUDED	51469
	AL 7075-T6510 SHAPES EXTRUDED	51470
	AL 7075-T6510 TUBE EXTRUDED	51471
AMS 4169	AL 7075-T6511 WIRE EXTRUDED	51472
	AL 7075-T6511 ROD EXTRUDED	51473
	AL 7075-T6511 BAR EXTRUDED	51474
	AL 7075-T6511 SHAPES EXTRUDED	51475
	AL 7075-T6511 TUBE EXTRUDED	51476
AMS 4170	AL 7075-T6 IMPACTS	51496
AMS 4172	AL 6061-T4511 BAR EXTRUDED	10020
	AL 6061-T4511 ROD EXTRUDED	50638
	AL 6061-T4511 SHAPES EXTRUDED	51336
	AL 6061-T4511 TUBE EXTRUDED	51344
AMS 4173	AL 6061-T6511 BAR EXTRUDED	50299
	AL 6061-T6511 ROD EXTRUDED	50648
	AL 6061-T6511 SHAPES EXTRUDED	51340
	AL 6061-T6511 TUBE EXTRUDED	51348
AMS 4179	AL 7175-T73652 FORGING HAND	50283
	AL 7175-T7452 FORGING HAND	51545
AMS 4182	AL 5056-O WIRE ROLLED	50615
AMS 4184	BRAZE AL ALLOY 4145 WIRE	10434
	AL 4145 METAL BRAZING FILLER	51823
AMS 4185	AL 4047 METAL BRAZING FILLER	51832
AMS 4187	AL 7075-O WIRE ROLLED	50674
	AL 7075-O BAR ROLLED	51385
	AL 7075-O BAR COLD FINISHED	51386
	AL 7075-O BAR DRAWN	51426
	AL 7075-O WIRE COLD FINISHED	52911
	AL 7075-O ROD ROLLED	52912
	AL 7075-O ROD COLD FINISHED	52913
	AL 7075-O WIRE DRAWN	52914
	AL 7075-O ROD DRAWN	52915
AMS 4190	AL 4043-F ROD WELDING	51684
	AL 4043-F WIRE WELDING	51685
AMS 4191	AL 2319-F WIRE WELDING	51681
	AL 2319-F ROD WELDING	51682
AMS 4192	AL 2024-T361 SHEET	51091
	AL 2024-T361 PLATE	51092
AMS 4193	AL 2024-T861 SHEET	51093
	AL 2024-T861 PLATE	51094
AMS 4194	AL 2024-T361 SHEET CLAD	51203
	AL 2024-T361 PLATE CLAD	51204
AMS 4195	AL 2024-T861 SHEET CLAD	51208
	AL 2024-T861 PLATE CLAD	51209
AMS 4196	AL 7075-O SHEET CLAD W/7011	52465
	AL 7075-O PLATE CLAD W/7011	52469
AMS 4197	AL 7075-T6 SHEET CLAD W/7011	52466
	AL 7075-T651 PLATE CLAD W/7011	52471
AMS 4201	AL 7050-T7651 PLATE	52287
AMS 4202	AL 7475-T7351 PLATE	51566
AMS 4205	AL 7010-T7451 PLATE	51567
AMS 4207	AL 7475-T61 SHEET CLAD	50992
AMS 4210F	AL 355.0-T51 CASTINGS SAND	51561
AMS 4212E	AL 355.0-T6 CASTINGS SAND	51560

MSFC-HDBK-527 REV F 9999942 0005034 7

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
AMS 4214D	AL 355.0-T71 CASTINGS SAND	51559
AMS 4215	AL C355.0-T6 CASTING	10395
AMS 4217F	AL 356.0-T6 CASTINGS SAND	50516
AMS 4218	AL A356.0-T61 CASTINGS	10053
AMS 4222	AL 2420-T77 SAND CASTING (WAS 142)	52484
AMS 4229	AL KO-1-T7 CASTINGS	51224
AMS 4231	AL 2950-T6 SAND CASTING (WAS 195)	52486
AMS 4260	AL 356.0-T6 CASTINGS	10517
AMS 4260C	AL 356.0-T6 CASTINGS INVESTMENT	10052
AMS 4261	AL A356.0-T51 CASTING	10485
AMS 4261C	AL 356.0-T51 CASTINGS INVESTMENT	51225
AMS 4280E	AL 355.0-T71 CASTINGS PERMANENT MOLD	51558
AMS 4284E	AL 356.0-T6 CASTINGS PERMANENT MOLD	51226
AMS 4285A	AL 356.0-T6 CASTINGS CENTRIFUGAL	51227
AMS 4286D	AL 356.0-T51 CASTINGS PERMANENT MOLD	10050
AMS 4320	AL 7149-T73 FORGING DIE	51229
AMS 4340	AL 7050-T76511 WIRE EXTRUDED	52289
	AL 7050-T76511 ROD EXTRUDED	52290
	AL 7050-T76511 BAR EXTRUDED	52291
AMS 4341	AL 7050-T73511 WIRE EXTRUDED	52292
	AL 7050-T73511 ROD EXTRUDED	52293
	AL 7050-T73511 BAR EXTRUDED	52294
AMS 4342	AL 7050-T74511 WIRE EXTRUDED	52295
	AL 7050-T74511 ROD EXTRUDED	52296
	AL 7050-T74511 BAR EXTRUDED	52297
AMS 4343	AL 7149-T73510 EXTRUSIONS	51230
	AL 7149-T73511 EXTRUSIONS	51231
AMS 4344	AL 7175-T73511 EXTRUSIONS	51548
AMS 4602	COPPER BAR ANNEALED HARD TEMPER	10333
	COPPER ROD ANNEALED HARD TEMPER	50832
	COPPER SHAPES ANNEALED HARD TEMPER	50833
AMS 4631	AL BRONZE #637	10410
	AL BRONZE #639	50712
AMS 4635	AL BRONZE #623 BAR	10376
	AL BRONZE #623 FORGING	50680
AMS 4640	AL BRONZE #630 ROD 110 KSI	10257
	AL BRONZE #630 BAR 110 KSI	50681
	AL BRONZE #630 FORGING 110 KSI	50682
AMS 4676	MONEL K-500 ALLOY	10740
AMS 4701	COPPER ALLOY 102 WIRE	10354
AMS 4730	MONEL 400 67NI 30CU WIRE ANNEALED	10222
AMS 4764	BRAZE 52.5CU 38.5MN 9NI	10197
AMS 4765	BRAZE 56AG 42CU 2NI	10650
AMS 4767	BRAZE 92.5 AG 7.2 CU .22 LI	10339
AMS 4769	BRAZE EASY-FLO 45	10480
AMS 4770	BRAZE EASY-FLO 45	10480
AMS 4772	BRAZE 54AG 40CU 5ZN 1NI	10624
AMS 4773	BRAZE 60AG 30CU 10SN	10242
AMS 4774	BRAZE 63AG 28.5CU 6SN 2.5NI	10243
AMS 4775	BRAZE 73NI 4.5SI 14CR 3.1B4.5	10245
AMS 4777	BRAZE 82NI 4.5SI 7CR 3FE 3.1B	10479
AMS 4778	BRAZE 92NI 4.5SI 3.1B	10246
AMS 4779	BRAZE BNI-4 94NI 3.5SI 1.8B	10673
AMS 4783	BRAZE 50CO 8SI 19CR 17NI 4W.8B	10481
AMS 4786	BRAZE 70AU 8PD 22NI	10478

SPECIFICATION	DESIGNATION	MATCD
AMS 4787	BRAZE 82AU 18NI	10119
AMS 4880	AL BRONZE #630 CASTINGS BEARING 95 KSI	10258
AMS 4900	TITANIUM COMM PURE SHEET ANNEALED 55KSI	10054
	TITANIUM COMM PURE STRIP ANNEALED 55 KSI	50940
	TITANIUM COMM PURE PLATE ANNEALED 55 KSI	50941
AMS 4911	TITANIUM 6AL 4V SHEET ANNEALED	10065
	TITANIUM 6AL 4V STRIP ANNEALED	50948
	TITANIUM 6AL 4V PLATE ANNEALED	50949
AMS 4921	TITANIUM COMM PURE BAR ANNEALED 70 KSI	10444
	TITANIUM COMM PURE FORGING ANNEALED 70 K	50937
	TITANIUM COMM PURE RINGS ANNEALED 70 KSI	50938
AMS 4928	TITANIUM 6AL 4V BAR 120 KSI	10365
AMS 4943	TITANIUM 3AL 2.5V TUBE ANNEALED	10453
AMS 4954	WELD WIRE TI 6AL 4V	10739
AMS 4956	WELD WIRE TI 6AL 4V ELI BAR	10166
	WELD WIRE ELI TI 6AL 4V	10169
AMS 4959	STEEL T-I 13V 11CR 3AL SPRING WIRE	10696
	TITANIUM 13V-11CR-3A1	30144
AMS 4965	TITANIUM 6AL 4V BAR STA	10401
	TITANIUM 6AL 4V FORGING STA	50953
AMS 4967	TITANIUM 6AL 4V BAR 120 KSI	10365
	TITANIUM 6AL 4V BAR ANNEALED STA	10402
	TITANIUM 6AL 4V ROD ANNEALED	50952
AMS 4982	TITANIUM 45%CB BAR ANNEALED	10712
AMS 5132	STEEL HIGH CARBON >200 KSI	10515
	STEEL 0.90-1.30 CARBON BAR <180	10653
AMS 5221	NICKEL ALLOY 902 SPAN-C	10441
AMS 5225	NICKEL ALLOY 902 SPAN-C	10441
AMS 5342	CRES 17PH-4MO H1100 CASTING INVESTMENT	10361
AMS 5343	CRES 17PH-4MO 150KSI CASTING INVESTMENT	10156
AMS 5349	CRES 416 CASTINGS PRECISION INVESTMENT Q	53226
AMS 5352A	CRES 440C CASTINGS INVESTMENT ANNEALED	53131
AMS 5353	CRES 431 CASTING INVESTMENT HOT FINISHED	53272
	CRES 431 CASTING INVESTMENT NORMALIZED &	53274
AMS 5354	CRES GREEK ASCOLOY CASTINGS INVESTMENT Q	53310
AMS 5355	CRES 17PH-4MO H1025 CASTING INVESTMENT	10378
AMS 5358	CRES 302 CASTING INVESTMENT	10601
AMS 5360	CRES 316 CASTING INVESTMENT ANNEALED	10159
	CRES 316 CASTING	52741
AMS 5362	CRES 347 CASTING INVESTMENT ANNEALED	10157
AMS 5363	CRES 347 CASTING ANNEALED	52774
AMS 5372	CRES 431 CASTING ANNEALED	53264
	CRES 431 CASTING QUENCHED & TEMPERED	53265
	CRES 431 CASTING NORMALIZED & TEMPERED	53273
	CRES 431 CASTING AS CAST	53276
AMS 5376	CRES N-155 CASTINGS PRECISION INVESTMENT	53148
AMS 5382	HAYNES STELLITE 31 INVESTMENT CAST	30084
AMS 5385	HAYNES STELLITE 21 INVESTMENT CAST	30095
AMS 5388	HASTELLOY C CASTING INVESTMENT ANNEALED	10158
AMS 5397	INCONEL 100 CASTING INVESTMENT	10745
AMS 5398	CRES 17PH-4MO H1000 CASTING SAND	10489
AMS 5500	CRES 18-8 SHIM STOCK	10606
AMS 5501	CRES 304 1/4 HARD FOIL COLD ROLL	10432
AMS 5504	CRES 410 PLATE ANNEALED	50814
AMS 5505	CRES 12CR FERRITE CONTROLLED SHEET ANNEA	53257

MSFC-HDBK-527 REV F 9999942 0005035 9

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
AMS 5505	CRES 12CR FERRITE CONTROLLED STRIP ANNEA	53258
	CRES 12CR FERRITE CONTROLLED PLATE ANNEA	53259
AMS 5506	CRES 420	50503
	CRES 420 PLATE	52437
	CRES 420 SHEET	52438
	CRES 420 STRIP	52439
AMS 5507	CRES 316L SHEET ANNEALED	10096
	CRES 316L PLATE ANNEALED	50801
	CRES 316L STRIP ANNEALED	50802
AMS 5508	CRES GREEK ASCOLOY SHEET ANNEALED	53306
	CRES GREEK ASCOLOY STRIP ANNEALED	53307
	CRES GREEK ASCOLOY PLATE ANNEALED	53308
	CRES GREEK ASCOLOY SHEET QUENCHED & TEMP	53317
	CRES GREEK ASCOLOY STRIP QUENCHED & TEMP	53318
	CRES GREEK ASCOLOY PLATE QUENCHED & TEMP	53319
AMS 5510	CRES 321 SHEET ANNEALED	10097
	CRES 321 PLATE ANNEALED	50808
	CRES 321 STRIP ANNEALED	50809
AMS 5511	CRES 304L SHEET ANNEALED	10092
	CRES 304L PLATE ANNEALED	50790
	CRES 304L STRIP ANNEALED	50791
AMS 5512	CRES 347 SHEET ANNEALED	10099
	CRES 347 PLATE ANNEALED	50810
	CRES 347 STRIP ANNEALED	50811
AMS 5513	CRES 304 PLATE ANNEALED	10090
	CRES 304 SHEET ANNEALED	50777
	CRES 304 STRIP ANNEALED	50778
AMS 5514	CRES 305 SHEET	10475
	CRES 305 PLATE	50793
	CRES 305 STRIP	50794
AMS 5516	CRES 302 SHEET	10262
	CRES 302 PLATE	50771
	CRES 302 STRIP	50772
AMS 5517	CRES 301 SHEET ANNEALED 1/2 HARD 125KSI	10088
	CRES 301 STRIP ANNEALED 1/2 HARD 125 KSI	50763
AMS 5520	CRES 15PH-7MO SHEET	10264
	CRES 15PH-7MO STRIP	50729
	CRES 15PH-7MO PLATE	50730
AMS 5522	CRES 314 PLATE ANNEALED	52724
	CRES 314 SHEET ANNEALED	52725
	CRES 314 PLATE HOT ROLLED	52726
	CRES 314 SHEET COLD ROLLED	52727
	CRES 314 STRIP ANNEALED	52728
	CRES 314 STRIP COLD ROLLED	52729
AMS 5524	CRES 316 BAR CONDITION A	10370
AMS 5525	CRES A286 SHEET 140KSI UTS	10124
	CRES A286 FASTENER MATERIAL SH	10267
	CRES A286 PLATE 140KSI UTS	50709
AMS 5525B	CRES A286 SHEET ANNEALED	53418
	CRES A286 STRIP ANNEALED	53419
	CRES A286 PLATE ANNEALED	53420
	CRES A286 STRIP 140KSI UTS	53421
	CRES A286 SHEET >140KSI, UTS	53429
AMS 5526	CRES 19-9DL SHEET ANNEALED	10702
	CRES 19-9DL PLATE ANNEALED	51169
AMS 5526	CRES 19-9DL STRIP ANNEALED	52429
AMS 5528	CRES 17PH-7MO RH900 SHEET	30077
	CRES 17PH-7MO SHEET CONDITION A	30121
	CRES 17PH-7MO PLATE CONDITION A	50752
	CRES 17PH-7MO STRIP CONDITION A	50753
	CRES 17PH-7MO RH900 PLATE	50755
	CRES 17PH-7MO RH900 STRIP	50756
	CRES 17PH-7MO TH1050 STRIP	53324
	CRES 17PH-4MO PLATE TH1050	53325
AMS 5529	CRES 17PH-7M0 CH900 SHEET	10409
	CRES 17PH-7MO CH900 STRIP	50750
AMS 5532	CRES N-155 SHEET ANNEALED	53146
	CRES N-155 STRIP ANNEALED	53153
	CRES N-155 PLATE ANNEALED	53154
AMS 5536	HASTELLOY X SHEET	10374
	HASTELLOY X STRIP	50844
	HASTELLOY X PLATE	50845
AMS 5537	HAYNES 25 SHEET ANNEALED	10144
	HAYNES 25 PLATE ANNEALED	50849
AMS 5540	INCONEL 600 SHEET ANNEALED	10134
	INCONEL 600 PLATE ANNEALED	50857
	INCONEL 600 STRIP ANNEALED	50858
AMS 5542	INCONEL X750 STRIP EXTRUDED	10136
	INCONEL X750 STRIP STA	10400
	INCONEL X750 SHEET ANNEALED	10450
	INCONEL X750 PLATE ANNEALED	50851
	INCONEL X750 PLATE STA	50854
AMS 5545	RENE 41 SHEET	10446
	RENE 41 STRIP	50895
	RENE 41 PLATE	50896
AMS 5546	CRES AM-350 SHEET COLD ROLLED & TEMPERED	53285
	CRES AM-350 SHEET CONDITION H	53286
	CRES AM-350 STRIP COLD ROLLED & TEMPERED	53287
	CRES AM-350 STRIP CONDITION H	53288
	CRES AM-350 SHEET CONDITION L	53294
	CRES AM-350 SHEET DA	53295
	CRES AM-350 SHEET BRAZED AND HEAT TREATE	53298
AMS 5548	AM 350 SCT 850 SHEET	10207
	AM 350 SCT 1000 SHEET	10738
	AM 350 SCT 100 STRIP	50683
	AM 350 SCT 850 STRIP	50684
	CRES AM-350 SCT850 SHEET	53283
	CRES AM-350 SCT850 STRIP	53284
AMS 5552	INCOLOY 801 PLATE ANNEALED	53092
	INCOLOY 801 STRIP ANNEALED	53093
AMS 5553	NICKEL 200 SHEET LOW CARBON	10225
	NICKEL 200 STRIP LOW CARBON	50890
	NICKEL 201 SHEET LOW CARBON	50891
	NICKEL 201 STRIP LOW CARBON	50892
AMS 5554	CRES AM-350 SCT1000 TUBE	10084
	CRES AM-350 TUBE DA	53289
AMS 5556	CRES 341 TUBE ANNEALED SEAMLESS	10102
	CRES 347 TUBE ANNEALED	10227
AMS 5557	CRES 321 TUBE ANNEALED SEAMLESS	10101
AMS 5560	CRES 304 TUBE/PTFE ANNEALED	10413

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
AMS 5568	CRES 17PH-7MO TUBE WELDED CONDITION A	53329
	CRES 17PH-7MO TH1050 TUBE WELDED	53330
AMS 5570	CRES 321 TUBE ANNEALED SEAMLESS	10101
AMS 5571	CRES 341 TUBE ANNEALED SEAMLESS	10102
AMS 5573	CRES 316 TUBE SEAMLESS	10474
	CRES 316 TUBE ANNEALED	52736
AMS 5576	CRES 321 TUBE ANNEALED SEAMLESS	10101
AMS 5580	INCONEL 600 TUBE ANNEALED	10038
AMS 5585	CRES N-155 TUBE WELDED ANNEALED	53147
	CRES N-155 TUBE ANNEALED	53155
AMS 5589	INCONEL 718 TUBE	10287
AMS 5590	INCONEL 718 TUBE ST1950F	10286
AMS 5592	RA 330 NI-CR-FE-SI ALLOY	10746
AMS 5595	CRES 21-6-9 SHEET ANNEALED	10103
	CRES 21-6-9 PLATE ANNEALED	50761
	CRES 21-6-9 STRIP ANNEALED	50762
AMS 5598	INCONEL X750 STRIP EXTRUDED	10136
	INCONEL X750 SHEET ANNEALED	10450
	INCONEL X750 PLATE ANNEALED	50851
AMS 5599	INCONEL 625 STRIP ANNEALED	10141
	INCONEL 625 SHEET ANNEALED	10404
	INCONEL 625 BAR	10727
	INCONEL 625 PLATE ANNEALED	50862
AMS 5603	CRES 14PH-8MO H1050 SHEET	10081
	CRES 14PH-8MO H1050 STRIP	50719
AMS 5604	CRES 17PH-4MO H1025 PLATE	50733
	CRES 17PH-4MO H1150M PLATE	50743
	CRES 17PH-4MO H1150M STRIP	50744
AMS 5605	INCONEL 706 SHEET	10209
	INCONEL 706 PLATE	50877
	INCONEL 706 STRIP	50878
AMS 5608	HAYNES 188 SHEET ANNEALED	10397
	HAYNES 188 PLATE ANNEALED	50847
AMS 5609	CRES 12CR FERRITE CONTROLLED SHEET ANNEA	53257
	CRES 12CR FERRITE CONTROLLED STRIP ANNEA	53258
	CRES 12CR FERRITE CONTROLLED PLATE ANNEA	53259
	CRES 410CB BAR QUENCHED & TEMPERED	53301
	CRES 410CB BAR ANNEALED	53302
	CRES 410CB FORGING QUENCHED & TEMPERED	53303
	CRES 410CB TUBING MECHANICAL QUENCHED &	53304
	CRES 410CB FORGING STOCK QUENCHED & TEMP	53305
AMS 5610	CRES 416 BAR ANNEALED	30075
	CRES 416 FORGING ANNEALED	53230
AMS 5611	CRES 12CR FERRITE CONTROLLED BAR QUENCHE	53260
	CRES 12CR FERRITE CONTROLLED FORGING QUE	53261
	CRES 12CR FERRITE CONTROLLED TUBE QUENCH	53262
	CRES 12CR FERRITE CONTROLLED FORGING STO	53263
AMS 5612	CRES 12CR FERRITE CONTROLLED BAR QUENCHE	53260
	CRES 12CR FERRITE CONTROLLED FORGING QUE	53261
	CRES 12CR FERRITE CONTROLLED TUBE QUENCH	53262
	CRES 12CR FERRITE CONTROLLED FORGING STO	53263
AMS 5614	CRES 12CR-0.5MO BAR TEMPERED	53118
	CRES 12CR-0.5MO FORGING TEMPERED	53119
	CRES 12CR-0.5MO STOCK FORGING TEMPERED	53120
AMS 5616	CRES GREEK ASCOLOY BAR QUENCHED & TEMPER	30090
AMS 5616	CRES GREEK ASCOLOY FORGING QUENCHED AND	50686
	CRES GREEK ASCOLOY TUBE QUENCHED & TEMPE	50687
	CRES GREEK ASCOLOY WIRE COLD FINISHED	53309
	CRES GREEK ASCOLOY BAR ANNEALED	53311
	CRES GREEK ASCOLOY TUBE COLD FINISHED	53316
AMS 5617	CRES CUSTOM 455 H1000	10694
	CRES CUSTOM 455 H950	30126
AMS 5622	CRES 17PH-4MO H1075 FORGING	10430
	CRES 17PH-4MO H1075 TUBE	10688
	CRES 17PH-4MO H1075 BAR	10693
	CRES 17PH-4MO H1075 RING	52428
AMS 5627	CRES 430 BAR ANNEALED	30066
	CRES 430 SHAPES ANNEALED	52440
	CRES 430 FORGING ANNEALED	52441
	CRES 430 WIRE ANNEALED	52442
AMS 5628	CRES 431 WIRE COLD FINISHED	53267
	CRES 431 BAR COLD FINISHED	53268
	CRES 431 TUBING MECHANICAL COLD FINISHED	53269
	CRES 431 BAR HOT FINISHED	53271
	CRES 431 WIRE SOFT	53275
AMS 5629	CRES 13PH-8MO H1050 BAR	10285
	CRES 13PH-8MO H1025 BAR	10343
	CRES 13PH-8MO H1100 BAR	10344
	CRES 13PH-8MO H1150	10643
	CRES 13PH-8MO H1000 BAR	30113
	CRES 13PH-8MO H950 BAR	50213
	CRES 13PH-8MO H1000 FORGING	50713
	CRES 13PH-8MO H1025 FORGING	50714
	CRES 13PH-8MO H1100 FORGING	50715
	CRES 13PH-8MO H950 FORGING	50716
	CRES 13PH-8MO H1050 FORGING	50718
AMS 5629A	CRES 13PH-8MO RH950 BAR	53433
	CRES 13PH-8MO H1150 BAR	53434
	CRES 13PH-8MO H1150M BAR	53435
	CRES 13PH-8MO BCHT950 FORGING	53442
	CRES 13PH-8MO H950 BAR ROUND	53446
	CRES 13PH-8MO H950 BAR HEX	53447
	CRES 13PH-8MO H950 BAR SQUARE	53448
	CRES 13PH-8MO H950 BAR FLAT	53449
	CRES 13PH-8MO H1000 BAR ROUND	53450
	CRES 13PH-8MO H1000 BAR HEX	53451
	CRES 13PH-8MO H1000 BAR SQUARE	53452
	CRES 13PH-8MO H1000 BAR FLAT	53453
	CRES 13PH-8MO H1025 BAR ROUND	53454
	CRES 13PH-8MO H1025 BAR HEX	53455
	CRES 13PH-8MO H1025 BAR SQUARE	53456
	CRES 13PH-8MO H1025 BAR FLAT	53457
	CRES 13PH-8MO H1050 BAR ROUND	53458
	CRES 13PH-8MO H1050 BAR HEX	53459
	CRES 13PH-8MO H1050 BAR SQUARE	53460
	CRES 13PH-8MO H1050 BAR FLAT	53461
	CRES 13PH-8MO H1100 BAR ROUND	53462
	CRES 13PH-8MO H1100 BAR HEX	53463
	CRES 13PH-8MO H1100 BAR SQUARE	53464
	CRES 13PH-8MO H1100 BAR FLAT	53465

MSFC-HDBK-527 REV F ■ 9999942 0005037 2 ■

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
AMS 5629A	CRES 13PH-8MO H1150 BAR ROUND	53466
	CRES 13PH-8MO H1150 BAR HEX	53467
	CRES 13PH-8MO H1150 BAR SQUARE	53468
	CRES 13PH-8MO H1150 BAR FLAT	53469
	CRES 13PH-8MO H950 RINGS FLASH WELDED	53470
	CRES 13PH-8MO H1000 RINGS FLASH WELDED	53472
	CRES 13PH-8MO H1025 RINGS FLASH WELDED	53474
	CRES 13PH-8MO H1050 RINGS FLASH WELDED	53476
	CRES 13PH-8MO H1100 FORGING	53478
	CRES 13PH-8MO H1100 RINGS FLASH WELDED	53479
	CRES 13PH-8MO H1150 FORGING	53481
	CRES 13PH-8MO RINGS FLASH WELDED	53482
AMS 5630C	CRES 440C BAR COLD FINISHED	30008
	CRES 440C FORGING ANNEALED	50825
AMS 5631	CRES 440A BAR COLD FINISHED	53137
	CRES 440A FORGING ANNEALED	53140
AMS 5632C	CRES 440F WIRE COLD FINISHED	53110
	CRES 440F BAR ANNEALED	53111
AMS 5636	CRES 302 BAR COLD DRAWN 100KSI	10089
AMS 5637	CRES 302 BAR COLD DRAWN 125KSI	10423
	CRES 302 WIRE	10520
AMS 5639	CRES 304 BAR ANNEALED	10351
	CRES 304 FORGING (CRES 30304)	50721
	CRES 304 FORGING ANNEALED	50775
	CRES 304 TUBE ANNEALED	50776
AMS 5640	CRES 303 BAR FREE MACHINE	30080
	CRES 303 FORGING FREE MACHINE	50773
AMS 5641	CRES 303SE BAR COLD FINISHED	52747
	CRES 303SE BAR SOLUTION TREATED	52748
	CRES 303SE FORGING SOLUTION TREATED	52751
AMS 5643	CRES 17PH-4MO H1025 BAR	10399
	CRES 17PH-4MO H1075 FORGING	10430
	CRES 17PH-4MO H1150M BAR	10435
	CRES 17PH-4MO H1100 BAR	10471
	CRES 17PH-4MO H1050 BAR	10476
	CRES 17PH-4MO H1075 BAR	10693
	CRES 17PH-4MO H900 BAR	30159
	CRES 17PH-4MO H950 BAR	50098
	CRES 17PH-4MO H1025 ROD	50731
	CRES 17PH-4MO H1025 RING	50732
	CRES 17PH-4MO H1050 FORGING	50735
	CRES 17PH-4MO H1050 TUBE	50736
	CRES 17PH-4MO H1150M RING	50740
	CRES 17PH-4MO H1150M FORGING	50741
	CRES 17PH-4MO H900 FORGING	50746
	CRES 17PH-4MO H900 TUBE	50747
	CRES 17PH-4MO H950 FORGING	50748
	CRES 17PH-4MO H950 TUBE	50749
	CRES 17PH-4MO H1075 RING	52428
AMS 5644	CRES 17PH-7MO TH1050 FORGING	50757
	CRES 17PH-7MO BAR CONDITION A	53340
	CRES 17PH-7MO FORGING CONDITION A	53341
AMS 5645	CRES 321 BAR ANNEALED	10098
	CRES 321 FORGING ANNEALED	50806
	CRES 321 BAR COLD FINISHED	52720
AMS 5646	CRES 347 BAR ANNEALED	52773
AMS 5647	CRES 304L ROD ANNEALED	10306
	CRES 304L FORGING	50786
	CRES 304L TUBE	50787
AMS 5649	CRES 316 FORGING ANNEALED	52740
AMS 5652	CRES 314 WIRE ANNEALED	52721
	CRES 314 WIRE COLD FINISHED	52722
	CRES 314 BAR ANNEALED	52723
	CRES 314 TUBE ANNEALED MECHANICAL	52730
	CRES 314 TUBE COLD FINISHED MECHANICAL	52731
	CRES 314 BAR COLD FINISHED	52732
	CRES 314 BAR HOT FINISHED	52733
	CRES 314 FORGING	52734
AMS 5655	CRES 12.5CR-1W BAR ANNEALED & TEMPERED	53143
	CRES 12.5CR-1W FORGING STOCK ANNEALED &	53145
AMS 5656	CRES 21-6-9 BAR ANNEALED	10104
	CRES 21-6-9 FORGING ANNEALED	50759
	CRES 21-6-9 RINGS ANNEALED	50760
AMS 5659	CRES 15PH-5MO H1150M FORGING	10386
	CRES 15PH-5MO H1150 BAR	10387
	CRES 15PH-5MO H1075 BAR	10388
	CRES 15PH-5MO H1025 BAR	10389
	CRES A286 BAR 130-190KSI	10518
	CRES 15PH-5MO H900 BAR	30160
	CRES 15PH-5MO H1025 FORGING	50723
	CRES 15PH-5MO H1075 FORGING	50726
	CRES 15PH-5MO H1150 FORGING	50727
AMS 5662	INCONEL 718 FORGING ST1775F	10505
	INCONEL 718 RINGS ST1775F	50873
AMS 5663	INCONEL 718 BAR	10406
AMS 5664	INCONEL 718 FORGING ST1775F	10505
	INCONEL 718 RINGS ST1775F	50873
AMS 5665	INCONEL 600 BAR ANNEALED	10135
	INCONEL 600 FORGING ANNEALED	50855
	INCONEL 600 RINGS ANNEALED	50856
AMS 5666	INCONEL 625 BAR	10727
	INCONEL 625 PLATE	50863
AMS 5667	INCONEL X750 BAR STA	10139
	INCONEL X750 FORGING STA	50852
	INCONEL X750 RINGS STA	50853
AMS 5673	CRES 302 CONDITION B	50229
AMS 5678	CRES 17PH-7MO CH900 WIRE	10147
	CRES 17PH-7MO SHEET CONDITION C	10451
	CRES 17PH-7MO WIRE CONDITION C	10516
AMS 5679	WELD WIRE NI BASE INCO 62	10190
AMS 5682	WIRE NICHROME V COATING ALLOY	10658
	WIRE 75NI 20CR RESIST EVANOPHM	10663
AMS 5685	CRES 302 WIRE	10520
AMS 5687	INCONEL 600 WIRE ANNEALED	10009
AMS 5688	CRES 302 WIRE SPRING TEMPER B	10391
	CRES 18-9 WIRE SPRING TEMPER	10419
AMS 5689	CRES 321 WIRE ANNEALED	52719
AMS 5690	CRES 316 WIRE ANNEALED	52737
	CRES 316 WIRE SOFT	52738
AMS 5697	CRES 304 WIRE ANNEALED	10220

MSFC-HDBK-527 REV F 9999942 0005038 4

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
AMS 5698	WIRE ALLOY X750 #1 TEMPER	10231
AMS 5699	WIRE ALLOY X750 SPRING TEMPER	10150
AMS 5701	INCONEL 706 BAR STA	10280
AMS 5703	INCONEL 706 BAR STA	10280
	INCONEL 706 FORGING STA	50879
	INCONEL 706 RINGS STA	50880
AMS 5708	WASPALOY BAR FORGING	30125
AMS 5712	RENE 41 BAR	10373
	RENE 41 RINGS	50894
AMS 5713	RENE 41 BAR	10373
	RENE 41 FORGING	50893
	RENE 41 RINGS	50894
AMS 5731	CRES A286 BAR 140 KSI	10011
	CRES A286 FASTENER MATERIAL SH	10267
	CRES A286 BAR 180KSI	50084
	CRES A286 TUBE 140KSI	50708
	CRES A286 TUBE 130-140KSI UTS	53422
	CRES A286 RINGS 130-140KSI, UTS	53430
AMS 5732	CRES A286 SHAPE	10392
	CRES A286 BAR 130-140KSI UTS	10456
AMS 5732B	CRES A286 TUBE 130-140KSI UTS	53422
	CRES A286 BAR QUENCHED	53426
	CRES A286 BAR >140KSI UTS	53427
	CRES A286 RINGS 130-140KSI, UTS	53430
AMS 5733	CRES DISCALOY	10718
AMS 5734	CRES A286 FORGING 140KSI	10125
	CRES A286 FASTENER MATERIAL SH	10267
AMS 5734A	CRES A286 BAR ANNEALED	53425
AMS 5735	CRES A286 FASTENER MATERIAL SH	10267
AMS 5736	CRES A286 FASTENER MATERIAL SH	10267
AMS 5737	CRES A286 FASTENER MATERIAL SH	10267
AMS 5738	CRES 303SE BAR HI-TENSION	52753
AMS 5742	INCOLOY 801 FORGING ANNEALED	53090
	INCOLOY 801 FORGING AGED	53091
	INCOLOY 801 BAR AGED	53096
	INCOLOY 801 RINGS FLASH WELDED	53098
	INCOLOY 801 STOCK	53099
AMS 5743	AM 355 SCT 1000 FORGING	10085
AMS 5745	CRES AM-350 SCT1000 BAR	53290
	CRES AM-350 SCT1000 FORGING	53291
	CRES AM-350 SCT850 BAR	53292
	CRES AM-350 BAR DA	53293
AMS 5753	NICKEL U-500 ST BAR	10132
	NICKEL U-500 ST FORGING	50876
AMS 5754	HASTELLOY X SHEET	10374
	HASTELLOY X PLATE	50845
AMS 5758	MULTIPHASE MP35N	10123
AMS 5759	HAYNES 25 BAR ANNEALED	10145
	HAYNES 25 FORGING ANNEALED	50848
AMS 5763	CRES CUSTOM 450 BAR ANNEALED	53202
	CRES CUSTOM 450 H900 BAR	53203
	CRES CUSTOM 450 H1050 BAR	53204
	CRES CUSTOM 450 H950 BAR	53205
	CRES CUSTOM 450 H1000 BAR	53206
	CRES CUSTOM 450 H1100 BAR	53207
AMS 5763	CRES CUSTOM 450 H1150 BAR	53208
AMS 5772	HAYNES 188 BAR ANNEALED	10297
	HAYNES 188 FORGING ANNEALED	50846
AMS 5773	CRES CUSTOM 450 BAR ANNEALED	53202
	CRES CUSTOM 450 H900 BAR	53203
	CRES CUSTOM 450 H1050 BAR	53204
	CRES CUSTOM 450 H950 BAR	53205
	CRES CUSTOM 450 H1000 BAR	53206
	CRES CUSTOM 450 H1100 BAR	53207
	CRES CUSTOM 450 H1150 BAR	53208
AMS 5774	CRES AM-350 WIRE WELDING	53300
AMS 5775	CRES AM-350 ELECTRODES WELDING	53299
AMS 5782	WELD WIRE CRES 349	10323
AMS 5784	WELD WIRE CRES 29-9	10655
AMS 5786	WELD WIRE NI BASE HASTELLOY W	10188
AMS 5801	WELD WIRE CO BASE HAYNES 188	10194
AMS 5817	CRES GREEK ASCOLOY WELD METAL QUENCHED &	53320
AMS 5832	WELD WIRE NI BASE INCO 718	10189
AMS 5837	WELD WIRE NI BASE INCO 625	10193
AMS 5840	CRES 13PH-8MO H950 WIRE	53432
AMS 5842	MP 159	51078
AMS 5870	INCONEL 601 SHEET ANNEALED	10140
	INCONEL 601 PLATE ANNEALED	50859
	INCONEL 601 STRIP ANNEALED	50860
AMS 6260T	STEEL 9310 BAR ANNEALED	53246
AMS 6265	STEEL 9310 FORGING	50935
	STEEL 9310 TUBE	50936
AMS 6265F	STEEL 9310 HOT ROLLED BAR	30073
	STEEL 9310 BAR ANNEALED	53246
AMS 6267B	STEEL 9310 BAR ANNEALED	53246
AMS 6274	STEEL 8620 BAR CAS-HD >200 KSI	30074
	STEEL 8620 CAS-HD TUBE >200 KSI	50520
	STEEL 8620 CAS-HD FORGING >200 KSI	50521
AMS 6282	STEEL 8735 TUBE NORMALIZED	53195
AMS 6294	STEEL 4620 BAR 165KSI	10284
AMS 62CD	STEEL 9NI 4CO (0.20C) PLATE 180-215 KSI	52686
AMS 62CF	STEEL 9NI 4CO (0.20C) FORGING 180-215 KS	52688
AMS 6304	STEEL 17-22A BAR FORGING TUBE	10726
AMS 6320	STEEL 8735 BARS	53193
	STEEL 8735 FORGING	53194
	STEEL 8735 ROUNDS <180 KSI UTS	53197
AMS 6322	STEEL 8740 BAR >200 KSI	30096
	STEEL 8740 FORGING >200 KSI	50927
	STEEL 8740 RING >200 KSI	50928
AMS 6322K	STEEL 8740 RINGS <200KSI	53171
AMS 6323G	STEEL 8740 TUBE <200 KSI UTS	53172
AMS 6350	STEEL 4130 SHEET 120-180 KSI	10108
	STEEL 4130 BAR 125-180 KSI	10109
	STEEL 4130 FORGING 125-180 KSI	50911
	STEEL 4130 PLATE 125-180 KSI	50912
AMS 6352	STEEL 4135 SHEET NORMALIZED	53156
	STEEL 4135 STRIP NORMALIZED	53157
	STEEL 4135 PLATE NORMALIZED	53158
	STEEL 4135 SHEET QUENCHED & TEMPERED	53161
AMS 6357	STEEL 8735 SHEET NORMALIZED	53190

MSFC-HDBK-527 REV F ■ 9999942 0005039 6 ■

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
AMS 6357	STEEL 8735 STRIP NORMALIZED	53191
	STEEL 8735 PLATE NORMALIZED	53192
	STEEL 8735 SHEET <180 KSI UTS	53196
AMS 6358F	STEEL 8740 SHEET <200 KSI UTS	53166
	STEEL 8740 STRIP <200 KSI UTS	53167
	STEEL 8740 PLATE <200 KSI UTS	53168
AMS 6359	STEEL 4344 SHEET ANNEALED	50054
	STEEL 4340 PLATE >200 KSI	50924
AMS 6365	STEEL 4135 ROUND QUENCHED & TEMPERED	53160
AMS 6372	STEEL 4135 TUBE NORMALIZED	53159
	STEEL 4135 TUBE QUENCHED & TEMPERED	53162
AMS 6382	STEEL 4140 BAR <201 KSI	10122
	STEEL 4140 FORGING <201 KSI	50913
	STEEL 4140 RING <201 KSI	50914
AMS 6407	STEEL 4330SI WROUGHT QUENCHED & TEMPERED	53177
	STEEL 4330SI SHEET QUENCHED & TEMPERED	53178
AMS 6414	STEEL 4340 BAR ANNEALED	50070
	STEEL 4340 FORGING ANNEALED	50916
	STEEL 4340 TUBE ANNEALED	50917
	STEEL 4340 FORGING >200 KSI	50920
	STEEL 4340 TUBE >200 KSI	50921
AMS 6415	DELETED SEE 50070	10301
	STEEL 4340 BAR ANNEALED	50070
	STEEL 4340 FORGING 180-200 KSI	50922
AMS 6418	STEEL HY-TUF FORGING QUENCHED AND TEMPER	52639
AMS 6419	STEEL 300M BAR 270-300 KSI UTS	52620
	STEEL 300M FORGING 270-300 KSI UTS	52621
AMS 6423	STEEL 98BV40 BAR >200KSI UTS	53121
	STEEL 98BV40 FORGING >200KSI UTS	53122
	STEEL 98BV40 TUBE >200KSI UTS	53123
AMS 6427	STEEL 4330V QUENCHED & TEMPERED 180-200	30165
AMS 6431	STEEL D6AC BAR TUBE,FORGING,CVEM 180KSI	30109
AMS 6440	STEEL 52100 TUBE 180-200 KSI	50518
AMS 6442	STEEL 50100 BAR 180-200 KSI	10737
	STEEL 50100 BEARING 180-200 KSI	50519
	STEEL 50100 FORGING 180-200 KSI	50925
AMS 6455	STEEL 6150 50C 1CR 25V	10492
AMS 6470	NITRALLOY 135MOD QUENCHED AND TEMPERED B	30063
	NITRALLOY 135MOD BAR COLD ROLLED	53242
	NITRALLOY 135MOD FORGING	53243
AMS 6485	STEEL H-11 BAR >200 KSI	30092
	STEEL H-11 FORGING >200 KSI	50850
AMS 6487	STEEL H-11 BAR >200 KSI	30092
	STEEL H-11 FORGING >200 KSI	50850
AMS 6490	STEEL TOOL M50 RC58-64 BAR	30038
	STEEL TOOL FORGING M50 RC58-64	50900
AMS 6491	STEEL TOOL M50 TUBE SPHEROIDIZE ANNEALED	52744
	STEEL TOOL M50 FORGING ANNEALED CVM	52745
AMS 6520	MARAGING 18NI (200) STEEL ANNEALED	52762
AMS 6523	STEEL 9NI 4CO (.20C) SHEET 180-200 KSI	10201
	STEEL 9NI 4CO (.20C) STRIP 190 KSI	50932
	STEEL 9NI 4CO (.20C) PLATE 190 KSI	50933
	STEEL 9NI 4C0 (0.20C) PLATE 180-215 KSI	52684
	STEEL 9NI 4CO (0.20C) PLATE 180-215 KSI	52686
	STEEL 9NI 4CO (0.20C) QUENCHED AND TEMPE	52695
AMS 6524	STEEL 9NI 4CO (0.30C) PLATE 220-240 KSI	52632
	STEEL 9NI 4CO (0.30C) SHEET 220-240 KSI	52634
	STEEL 9NI 4CO (0.30C) STRIP 220-240 KSI	52635
AMS 6525	STEEL 9NI 4CO BAR	10734
	STEEL 9NI 4CO (.20C) FORGING 180-200 KSI	50929
	STEEL 9NI 4CO (.20C) RING 180-200 KSI	50930
	STEEL 9NI 4CO (.30C) FORGING 180-200 KSI	50934
AMS 6526	STEEL 9NI 4CO (0.30C) TUBE 220-240 KSI U	52636
	STEEL 9NI 4CO (0.30C) BAR 220-240 KSI UT	52637
AMS 6535	STEEL 8735 TUBE NORMALIZED	53195
	STEEL 8735 TUBE <180 KSI UTS	53198
AMS 6540A	STEEL 9NI 4C0 (0.25C) TUBE 180-215 KSI U	52673
	STEEL 9NI 4C0 (0.25C) RINGS 180-215 KSI	52674
	STEEL 9NI 4C0 (0.25C) FORGING 180-215 KS	52679
AMS 6541A	STEEL 9NI 4C0 (0.25C) FORGING 180-215 KS	52678
AMS 6542A	STEEL 9NI 4CO (0.45C) FORGING QUENCHED/T	52654
	STEEL 9NI 4CO (0.45C) FORGING 260-290 KS	52655
	STEEL 9NI 4CO (0.45C) FORGING AUSTEMPERE	52656
AMS 6545A	STEEL 9NI 4C0 (0.25C) PLATE 180-215 KSI	52669
	STEEL 9NI 4C0 (0.25C) SHEET 180-215 KSI	52675
	STEEL 9NI 4C0 (0.25C) STRIP 180-215 KSI	52676
AMS 6546	STEEL 9NI 4C0 (0.25C) SHEET PREMIUM QUAL	52683
	STEEL 9NI 4CO (0.25C) STRIP PREMIUM QUAL	52696
AMS 6546A	STEEL 9NI 4C0 (0.25C) PLATE 180-215 KSI	52668
AMS 65CD	STEEL 9NI 4CO (0.20C) TUBE 180-215 KSI U	52689
	STEEL 9NI 4CO (0.20C) 180-215 KSI UTS	52690
	STEEL 9NI 4CO (0.20C) STRIP 180-215 KSI	52691
AMS 65CE	STEEL 9NI 4CO (0.30C) SHEET QUENCHED AND	52628
	STEEL 9NI 4CO (0.30C) STRIP QUENCHED AND	52629
	STEEL 9NI 4CO (0.30C) PLATE QUENCHED AND	52630
	STEEL 9NI 4CO (0.30C) PLATE 220-240 KSI	52631
AMS 7228	CRES 18-8 (303) WIRE	10675
AMS 7229	CRES 300 SERIES	10268
	CRES 347 RIVET CONDITION A	10671
AMS 7232	INCONEL 600 BAR ANNEALED	10135
AMS 7245	CRES CUSTOM 455 H1000	10694
AMS 7440	STEEL 52100 FORGING 180-200 KSI	50926
AMS 7445	CRES 440A BAR ANNEALED	30002
	CRES 440B BAR ANNEALED	50821
	CRES 440C BAR ANNEALED	50822
AMS 7479	CRES A286 FASTENERS 160KSI MIN UTS	50140
AMS 7701	MAGNET NI-FE SHEET MUMETAL	10118
	MAGNET HI-PERM MUMETAL	10235
	MAGNET NI-FE STRIP MUMETAL	50866
AMS 7705	MAGNET NI-FE ALLOY BAR NI77 CU5 CR1.5	10131
	MAGNET NI-FE ALLOY FORGING NI77 CU5 CR1.	50888
AMS 7711	STEEL M36 1.5%SI <180KSI	50067
AMS 7718	MAGNET 50NI 50FE BAR	10250
	MAGNET 50NI 50FE FORGING	50867
	MAGNET 50NI 50FE TUBE	50868
AMS 7719	MAGNET NI-FE ALLOY SHEET	10215
	MAGNET NI-FE ALLOY PLATE	51171
AMS 7720	LEAD ALLOY 6.5SB .5SN CASTING	30141
AMS 7725	TUNGSTEN MALLORY ALLOY 2000	30107
AMS 7726	NICKEL ALLOY 53 (GLASS SEALING)	30069

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
AMS 7727	NICKEL ALLOY 53 (GLASS SEALING)	30069
AMS 7728	NICKEL ALLOY 53 (GLASS SEALING)	30069
AMS 7735	PALINEY #7 COMP D	10608
AMS 7901	BERYLLIUM BAR	10709
AMS-5732	CRES A286 BAR 130-190KSI	10518
AMS5604	CRES 17PH-4MO H1150M SHEET	10076
ANS 6470	NITRALLOY 135MOD FORGING STOCK	53244
ANSI-C96 1-1964	T/C ALLOY PLATINUM TY RN WIRE	10668
ANSIC96.1-1964	T/C ALLOY COPPER TY RN	10725
ARMCO 72-82-M22	MAGNET ALLEGHENY LUDLUM	10697
ASM 4500	COPPER 100% PLATE ANNEALED	50837
ASM 5712	RENE 41 FORGING	50893
ASTM 225/7	AL 5052-O BAR ROLLED	51913
ASTM 6470	NITRALLOY 135MOD BAR HOT ROLLED	53241
ASTM A 276	CRES 304 BAR ANNEALED	10351
	CRES 304 FORGING ANNEALED	50775
ASTM A 296 GR 8	CRES 304 CASTING INVESTMENT ANNEALED	10674
ASTM A 312	CRES 321 TUBE ANNEALED SEAMLESS	10101
	CRES 316 TUBE SEAMLESS	10474
ASTM A 582	CRES 303 BAR FREE MACHINE	30080
	CRES 203EZ BAR ANNEALED	50502
ASTM A 682	STEEL HIGH CARBON >200 KSI	10515
ASTM A-240	CRES 304 PLATE	50085
	CRES 304 SHEET	50784
	CRES 304 STRIP	50785
ASTM A-47/A-197	IRON-MALLEABLE	10749
ASTM A-479 XM-27	CRES E-BRITE Z6-1 SHAPE	50710
	CRES E-BRITE Z6-1 WIRE	50711
ASTM A108	STEEL 1213 COLD FINISH <180KSI	30064
	STEEL 1215 COLD FINISH <180KSI	30065
ASTM A182	CRES 316 BAR CONDITION A	10370
ASTM A193	CRES 17PH-4MO H1150M FORGING EXTRUDED	50742
	CRES 316 MATERIAL BOLTING	52742
ASTM A228/ASS8M	STEEL 1095 (SPRING)	30142
ASTM A276	CRES 316 BAR CONDITION A	10370
	CRES 403 BAR ANNEALED	53234
	CRES 403 BAR TEMPERED	53235
	CRES 403 BAR COLD DRAWN	53236
	CRES 403 BILLET	53240
ASTM A296	CRES 303SE CASTING SOLUTION TREATED	52752
	CRES 303SE BAR CAST	52756
ASTM A313	CRES 302 SPRING CONDITION B WIRE	10148
	CRES 316 SPRING WIRE CONDITION B	10296
	CRES 304 SPRING WIRE FULL HARD	10645
ASTM A314	CRES 347 FORGING ANNEALED	52775
	CRES 403 BAR TEMPERED	53235
	CRES 403 BILLET	53240
ASTM A320	CRES 303SE BOLTING MATERIAL SOLUTION TRE	52750
ASTM A351	CRES CK-20 CASTING ANNEALED HIGH TEMP SE	52705
	CRES HK CASTING HIGH TEMP SERVICE	52708
ASTM A355	NITRALLOY 135MOD BAR HOT ROLLED	53241
ASTM A366/A366M	STEEL 1010 <180KSI	10358
ASTM A36M	STEEL CARBON RC 29-33	10720
ASTM A451	CRES CK-20 PIPE ANNEALED CENTRIFUGAL CAS	52706
ASTM A473	CRES 347 FORGING ANNEALED	52775

SPECIFICATION	DESIGNATION	MATCD
ASTM A479	CRES 316 BAR CONDITION A	10370
	CRES XM-27 E-BRITE Z6-1 BAR	10661
ASTM A484	CRES 203EZ BAR ANNEALED	50502
ASTM A493	CRES 300 SERIES FASTENERS	50224
	CRES 400 SERIES FASTENERS	50225
ASTM A514	STEEL T-1A PLATE WELDED	53221
	STEEL T-1A PLATE WELDED & TEMPERED	53222
	STEEL T-1A SHEET	53223
	STEEL T-1A STRIP	53224
	STEEL T-1A PLATE <180 KSI UTS	53225
	STEEL T-1 PLATE <180 KSI UTS	53248
	STEEL T-1 PLATE WELDED	53249
	STEEL T-1 PLATE UNWELDED	53250
	STEEL T-1 PLATE WELDED & TEMPERED	53251
	STEEL T-1 BAR <180 KSI UTS	53252
	STEEL T-1 FLATS <180 KSI UTS	53253
	STEEL T-1 TUBE SEAMLESS <180 KSI UTS	53254
	STEEL T-1 WROUGHT <180 KSI UTS	53255
ASTM A514/A514M	STEEL T-1B PLATE	52703
ASTM A517	STEEL T-1A PLATE WELDED	53221
	STEEL T-1A PLATE WELDED & TEMPERED	53222
	STEEL T-1A SHEET	53223
	STEEL T-1A STRIP	53224
	STEEL T-1A PLATE <180 KSI UTS	53225
	STEEL T-1 PLATE <180 KSI UTS	53248
	STEEL T-1 PLATE WELDED	53249
	STEEL T-1 PLATE UNWELDED	53250
	STEEL T-1 PLATE WELDED & TEMPERED	53251
	STEEL T-1 BAR <180 KSI UTS	53252
	STEEL T-1 FLATS <180 KSI UTS	53253
	STEEL T-1 TUBE SEAMLESS <180 KSI UTS	53254
	STEEL T-1 STRIP	53256
ASTM A517/A517M	STEEL T-1B PLATE	52703
ASTM A538	MARAGING 18NI (200) SHEET STEEL AGED VAC	52757
	MARAGING 18NI (200) PLATE STEEL AGED AIR	52758
	MARAGING 18NI (200) PLATE STEEL AGED VAC	52759
	MARAGING 18NI (200) STEEL AGED AIR MELT	52760
	MARAGING 18NI (200) STEEL AGED VAC ARC R	52761
	MARAGING 18NI (200) STEEL ANNEALED	52762
	MARAGING 18NI (200) ROUNDS STEEL AGED	52763
	MARAGING 18NI (200) SHEET STEEL AGED	52764
	MARAGING 18NI (200) STEEL AGED	52765
	MARAGING 18NI (200) PLATE STEEL AGED	52766
	MARAGING 18NI (200) STEEL PLATE WELDED A	52767
ASTM A580	CRES 302 SPRING CONDITION B WIRE	10148
	CRES 316 SPRING WIRE CONDITION B	10296
	CRES 304 SPRING WIRE FULL HARD	10645
ASTM A581	CRES 203EZ WIRE COLD FINISHED	53126
ASTM A582	CRES 303/304 BAR	10506
	CRES 303/305 BAR	10512
	CRES 416 BAR ANNEALED	30075
	CRES 203EZ BAR COLD FINISHED	53127
ASTM A600	STEEL TOOL M2 RC 32-48 BARS	30039
	STEEL TOOL D2 RC 58-62 BARS	30040
ASTM A608	CRES HK CAST TUBE CENTRIFUGAL	52709

MSFC-HDBK-527 REV F 9999942 0005041 4

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
ASTM A686	STEEL TOOL CARBON VANAD <200KSI	10699
ASTM B 227	WIRE COPPER STEEL CLAD	10678
ASTM B 298	COPPER WIRE AG PLATE SOFT OR ANN	10469
ASTM B 344	WIRE NICHROME V COATING ALLOY	10658
	WIRE 75NI 20CR RESIST EVANOPHM	10663
ASTM B 387	MOLYBDENUM	30100
ASTM B 392	CB ROD	30129
ASTM B 477	BRAZE NEYORO AU-AG ALLOYS	10523
ASTM B 534	BE-CU #175 BAR	10716
ASTM B 563	PALINEY 6 PD-PT-AG-CU ALLOY	10713
ASTM B 61	BRONZE CASTING CA 922	10656
ASTM B-103	BRONZE PHOSPHOR-ALL FORMS	10322
ASTM B-124	BRASS,ALL FORM	10321
ASTM B-139	BRONZE PHOSPHOR-ALL FORMS	10322
ASTM B-152	COPPER BAR ANNEALED HARD TEMPER	10333
	COPPER ALLOY 110 STRIP	50826
	COPPER ALLOY 110 PLATE	50827
	COPPER ALLOY 110 ROD	50828
	COPPER ALLOY 110 BAR	50829
ASTM B-16	BRASS,ALL FORM	10321
ASTM B-160	NICKEL 200 STRIP LOW CARBON	50890
	NICKEL 201 SHEET LOW CARBON	50891
	NICKEL 201 STRIP LOW CARBON	50892
ASTM B-161	NICKEL 201 SHEET LOW CARBON	50891
	NICKEL 201 STRIP LOW CARBON	50892
ASTM B-162	NICKEL 200 STRIP LOW CARBON	50890
	NICKEL 201 SHEET LOW CARBON	50891
	NICKEL 201 STRIP LOW CARBON	50892
ASTM B-166	INCONEL 600 FORGING ANNEALED	50855
	INCONEL 600 RINGS ANNEALED	50856
ASTM B-168	INCONEL 600 PLATE ANNEALED	50857
	INCONEL 600 STRIP ANNEALED	50858
ASTM B-172	WIRE COPPER TIN PLATED	10330
ASTM B-187	COPPER ALLOY 110 STRIP	50826
	COPPER ALLOY 110 PLATE	50827
	COPPER ALLOY 110 ROD	50828
	COPPER ALLOY 110 BAR	50829
ASTM B-301	COPPER BAR ANNEALED HARD TEMPER	10333
	COPPER SHAPES ANNEALED HARD TEMPER	50833
ASTM B-36	BRASS,ALL FORM	10321
ASTM B-392	CB BAR	50700
	CB WIRE	50701
ASTM B-453	BRASS,ALL FORM	10321
ASTM B-98	COPPER 661/SIL ALLOY BAR	50839
	COPPER 661/SIL ALLOY SHAPE	50840
ASTM B121	COPPER 62CU CDA350 BRASS COPPER	10372
ASTM B122 #4	COPPER 55 18NI 27ZN ALLOY 770	10685
ASTM B152	COPPER ALLOY 110 SHEET	10346
ASTM B160	NICKEL 200 SHEET LOW CARBON	10225
ASTM B161	NICKEL 200 SHEET LOW CARBON	10225
ASTM B162	NICKEL 200 SHEET LOW CARBON	10225
ASTM B167	INCONEL 600 TUBE ANNEALED	10038
ASTM B168	INCONEL 600 SHEET ANNEALED	10134
	INCONEL X750 STRIP STA	10400
ASTM B170	COPPER ALLOY 102 WIRE	10354

SPECIFICATION	DESIGNATION	MATCD
ASTM B179	AL 1175-O CASTING SAND,MOLD,DIE	10684
ASTM B187	COPPER ALLOY 110 SHEET	10346
ASTM B194	BE-CU #175	10638
ASTM B209	AL 2124-T851 PLATE	10006
	AL 2219-T62 SHEET	10015
	AL 6061-T4 SHEET	10018
	AL 6061-T6 SHEET	10022
	AL 7075-T6 SHEET	10028
	AL 2219-T81 SHEET	10111
	AL 5052-H32 SHEET	10112
	AL 5052-H36 SHEET	10115
	AL 5456-H112 SHEET	10203
	AL 2024-T62 SHEET	10210
	AL 5456-H321 SHEET	10255
	AL 1100-O SHEET	10279
	AL 3003-O SHEET	10282
	AL 2024-O PLATE CLAD	10408
	AL 7075-T6 SHEET CLAD	10457
	AL 2014-T6 SHEET CLAD	10521
	AL 2024-T81 SHEET	10750
	AL 2024-T3 SHEET	30111
	AL 2024-O SHEET	30140
	AL 7178-T6 SHEET CLAD	30158
	AL 5652-O SHEET	30188
	AL 2219-T37 SHEET	50072
	AL 2219-T351 PLATE	50076
	AL 2219-T31 SHEET	50079
	AL 2219-T87 SHEET	50081
	AL 2219-T851 PLATE	50082
	AL 7075-T76 SHEET CLAD	50091
	AL 6061-O SHEET	50148
	AL 5052-O SHEET	50216
	AL 7075-T73 SHEET	50239
	AL 2014-T62 SHEET CLAD	50251
	AL 2024-T3 SHEET CLAD	50256
	AL 2024-T4 SHEET CLAD	50258
	AL 2024-T42 SHEET CLAD	50259
	AL 2024-T851 PLATE CLAD	50264
	AL 2024-T4 SHEET	50268
	AL 5052-H34 SHEET	50271
	AL 5052-H38 SHEET	50274
	AL 1100-O PLATE	50534
	AL 2014-T62 PLATE CLAD	50542
	AL 2024-T351 PLATE CLAD	50557
	AL 2024-T351 PLATE	50558
	AL 2024-T42 PLATE CLAD	50565
	AL 2024-T62 PLATE	50570
	AL 2024-T81 SHEET CLAD	50574
	AL 2024-O SHEET CLAD	50581
	AL 2219-T37 PLATE	50587
	AL 2219-T62 PLATE	50589
	AL 2219-T87 PLATE	50595
	AL 3003-O PLATE	50600
	AL 5052-H32 PLATE	50607
	AL 5052-H34 PLATE	50608

MSFC-HDBK-527 REV F 9999942 0005042 6

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
ASTM B209	AL 5052-O PLATE	50611
	AL 5456-H112 PLATE	50623
	AL 5456-H321 PLATE	50624
	AL 6061-T4 PLATE	50642
	AL 6061-T651 PLATE	50646
	AL 6061-O PLATE	50654
	AL 7075-T7351 PLATE	50669
	AL 7075-T7651 PLATE CLAD	50673
	AL 2024-T851 PLATE	50973
	AL 1100-H14 PLATE	50974
	AL 1100-H14 SHEET	50975
	AL 5086-O SHEET	50993
	AL 5086-O PLATE	50994
	AL 5086-H32 SHEET	50995
	AL 5086-H32 PLATE	50996
	AL 5086-H34 SHEET	50997
	AL 5086-H34 PLATE	50998
	AL 5086-H36 SHEET	50999
	AL 5086-H38 SHEET	51000
	AL 5086-H112 SHEET	51001
	AL 5086-H112 PLATE	51002
	AL 5086-H116 SHEET	51003
	AL 5086-H116 PLATE	51004
	AL 2219-O SHEET	51046
	AL 2219-O PLATE	51047
	AL 2024-O PLATE	51090
	AL 2024-T361 SHEET	51091
	AL 2024-T361 PLATE	51092
	AL 2024-T861 SHEET	51093
	AL 2024-T861 PLATE	51094
	AL 2024-T72 SHEET	51095
	AL 2024-T42 SHEET	51096
	AL 2024-T42 PLATE	51097
	AL 5154-O SHEET	51193
	AL 5154-H32 SHEET	51194
	AL 5154-H34 SHEET	51195
	AL 5154-H36 SHEET	51196
	AL 5154-H38 SHEET	51197
	AL 5154-O PLATE	51198
	AL 5154-H32 PLATE	51199
	AL 5154-H34 PLATE	51200
	AL 5154-H112 PLATE	51201
	AL 2024-T361 SHEET CLAD	51203
	AL 2024-T361 PLATE CLAD	51204
	AL 2024-T62 SHEET CLAD	51205
	AL 2024-T62 PLATE CLAD	51206
	AL 2024-T72 SHEET CLAD	51207
	AL 2024-T861 SHEET CLAD	51208
	AL 2024-T861 PLATE CLAD	51209
	AL 6061-T42 SHEET	51289
	AL 6061-T62 SHEET	51290
	AL 6061-T42 PLATE	51292
	AL 6061-T62 PLATE	51293
	AL 7075-O SHEET	51378
	AL 7075-O PLATE	51379

SPECIFICATION	DESIGNATION	MATCD
ASTM B209	AL 7075-T62 SHEET	51380
	AL 7075-T62 PLATE	51381
	AL 7075-T651 PLATE	51382
	AL 7075-T7651 PLATE	51384
	AL 2014-O SHEET	51504
	AL 2014-T3 SHEET	51505
	AL 2014-T4 SHEET	51506
	AL 2014-T42 SHEET	51507
	AL 2014-T6 SHEET	51508
	AL 2014-T62 SHEET	51509
	AL 2014-O PLATE	51510
	AL 2014-T42 PLATE	51511
	AL 2014-T451 PLATE	51512
	AL 2014-T62 PLATE	51513
	AL 2014-T651 PLATE	51514
	AL 2014-O SHEET CLAD	51549
	AL 2014-O PLATE CLAD	51550
	AL 2014-T3 SHEET CLAD	51551
	AL 2014-T4 SHEET CLAD	51552
	AL 2014-T42 SHEET CLAD	51553
	AL 2014-T42 PLATE CLAD	51554
	AL 2014-T451 PLATE CLAD	51555
	AL 2014-T651 PLATE CLAD	51556
	AL 3004-O SHEET	51594
	AL 3004-O PLATE	51595
	AL 3004-H32 SHEET	51596
	AL 3004-H32 PLATE	51597
	AL 3004-H34 SHEET	51598
	AL 3004-H34 PLATE	51599
	AL 3004-H36 SHEET	51600
	AL 3004-H38 SHEET	51601
	AL 3004-H112 PLATE	51602
	AL 3003-O SHEET CLAD	51609
	AL 3003-O PLATE CLAD	51610
	AL 3003-H12 SHEET CLAD	51611
	AL 3003-H12 PLATE CLAD	51612
	AL 3003-H14 SHEET CLAD	51613
	AL 3003-H14 PLATE CLAD	51614
	AL 3003-H16 SHEET CLAD	51615
	AL 3003-H18 SHEET CLAD	51616
	AL 3003-H112 PLATE CLAD	51617
	AL 5005-O SHEET	51645
	AL 5005-O PLATE	51646
	AL 5005-H12 SHEET	51647
	AL 5005-H12 PLATE	51648
	AL 5005-H14 SHEET	51649
	AL 5005-H14 PLATE	51650
	AL 5005-H16 SHEET	51651
	AL 5005-H18 SHEET	51652
	AL 5005-H32 SHEET	51653
	AL 5005-H32 PLATE	51654
	AL 5005-H34 SHEET	51655
	AL 5005-H34 PLATE	51656
	AL 5005-H36 SHEET	51657
	AL 5005-H38 SHEET	51658

MSFC-HDBK-527 REV F 9999942 0005043 8

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
ASTM B209	AL 5005-H112 PLATE	51659
	AL 5252-H24 SHEET	51678
	AL 5252-H25 SHEET	51679
	AL 5252-H28 SHEET	51680
	AL 5457-O SHEET	51701
	AL 3105-O SHEET	51702
	AL 3105-H12 SHEET	51703
	AL 3105-H14 SHEET	51704
	AL 3105-H16 SHEET	51705
	AL 3105-H18 SHEET	51706
	AL 3105-H25 SHEET	51707
	AL 3005-O SHEET	51708
	AL 3005-H12 SHEET	51709
	AL 3005-H14 SHEET	51710
	AL 3005-H16 SHEET	51711
	AL 3005-H18 SHEET	51712
	AL 3005-H19 SHEET	51713
	AL 3005-H26 SHEET	51714
	AL 3005-H28 SHEET	51715
	AL 5652-H32 SHEET	51717
	AL 5652-H34 SHEET	51718
	AL 5652-H36 SHEET	51719
	AL 5652-H38 SHEET	51720
	AL 5652-O PLATE	51721
	AL 5652-H32 PLATE	51722
	AL 5652-H34 PLATE	51723
	AL 5652-H112 PLATE	51724
	AL 5254-O SHEET	51727
	AL 5254-O PLATE	51728
	AL 5254-H32 SHEET	51729
	AL 5254-H32 PLATE	51730
	AL 5254-H34 SHEET	51731
	AL 5254-H34 PLATE	51732
	AL 5254-H36 SHEET	51733
	AL 5254-H38 SHEET	51734
	AL 5254-H112 PLATE	51735
	AL 5657-H241 SHEET	51748
	AL 5657-H25 SHEET	51749
	AL 5657-H26 SHEET	51750
	AL 5657-H28 SHEET	51751
	AL 3004-O SHEET CLAD	51752
	AL 3004-H32 SHEET CLAD	51753
	AL 3004-H34 SHEET CLAD	51754
	AL 3004-H36 SHEET CLAD	51755
	AL 3004-H38 SHEET CLAD	51756
	AL 3004-O PLATE CLAD	51757
	AL 3004-H32 PLATE CLAD	51758
	AL 3004-H34 PLATE CLAD	51759
	AL 3004-H112 PLATE CLAD	51760
	AL 5050-O SHEET	51794
	AL 5050-H32 SHEET	51795
	AL 5050-H34 SHEET	51796
	AL 5050-H36 SHEET	51797
	AL 5050-H38 SHEET	51798
	AL 5050-O PLATE	51799

SPECIFICATION	DESIGNATION	MATCD
ASTM B209	AL 5050-H112 PLATE	51800
	AL 5454-O SHEET	51885
	AL 5454-O PLATE	51886
	AL 5454-H32 SHEET	51887
	AL 5454-H32 PLATE	51888
	AL 5454-H34 SHEET	51889
	AL 5454-H34 PLATE	51890
	AL 5454-H112 PLATE	51891
	AL 5052-H112 PLATE	51956
	AL 1100-H12 SHEET	51957
	AL 1100-H12 PLATE	51958
	AL 1100-H16 SHEET	51959
	AL 1100-H18 SHEET	51960
	AL 1100-H112 PLATE	51961
	AL 1060-O SHEET	52056
	AL 1060-H12 SHEET	52057
	AL 1060-H14 SHEET	52058
	AL 1060-H16 SHEET	52059
	AL 1060-H18 SHEET	52060
	AL 1060-H112 SHEET	52061
	AL 1060-O PLATE	52062
	AL 1060-H12 PLATE	52063
	AL 1060-H14 PLATE	52064
	AL 1060-H112 PLATE	52065
	AL 7178-O SHEET	52174
	AL 7178-O PLATE	52175
	AL 7178-T6 SHEET	52176
	AL 7178-T62 SHEET	52177
	AL 7178-T62 PLATE	52178
	AL 7178-T651 PLATE	52179
	AL 7178-T76 SHEET	52180
	AL 7178-T7651 PLATE	52181
	AL 5456-O PLATE	52270
	AL 5456-H116 PLATE	52271
	AL 5456-O SHEET	52272
	AL 5456-H116 SHEET	52273
	AL 7075-O SHEET CLAD	52430
	AL 7075-T62 SHEET CLAD	52431
	AL 7075-O PLATE CLAD	52432
	AL 7075-T62 PLATE CLAD	52433
	AL 7075-T651 PLATE CLAD	52434
	AL 7075-T651 PLATE CLAD	52435
	AL 7075-O SHEET ONE SIDE CLAD	52448
	AL 7075-T6 SHEET ONE SIDE CLAD	52449
	AL 7075-T62 SHEET ONE SIDE CLAD	52450
	AL 7075-O PLATE ONE SIDE CLAD	52451
	AL 7075-T651 PLATE ONE SIDE CLAD	52453
	AL 7178-O SHEET CLAD	52475
	AL 7178-O PLATE CLAD	52476
	AL 7178-T6 PLATE CLAD	52477
	AL 7178-T62 SHEET CLAD	52478
	AL 7178-T62 PLATE CLAD	52479
	AL 7178-T651 PPLATE CLAD	52480
	AL 7178-T76 SHEET CLAD	52481
	AL 7178-T7651 PLATE CLAD	52482

MSFC-HDBK-527 REV F 9999942 0005044 T

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
ASTM B209	AL 3003-H12 SHEET	52961
	AL 3003-H12 PLATE	52962
	AL 3003-H14 SHEET	52963
	AL 3003-H14 PLATE	52964
	AL 3003-H16 SHEET	52965
	AL 3003-H18 SHEET	52966
	AL 3003-H112 PLATE	52967
	AL 7075-T76 SHEET	53026
	AL 2219-O PLATE CLAD	53083
ASTM B210	AL 6061-T4 TUBE DRAWN SEAMLESS	10021
	AL 6061-T6 TUBE DRAWN SEAMLESS	10025
	AL 1100-O TUBE	10340
	AL 2024-T3 TUBE DRAWN SEAMLESS	50554
	AL 5086-O TUBE DRAWN SEAMLESS	51020
	AL 5086-H32 TUBE DRAWM SEAMLESS	51021
	AL 5086-H34 TUBE DRAWN SEAMLESS	51022
	AL 5086-H36 TUBE DRAWN SEAMLESS	51023
	AL 2024-O TUBE DRAWN SEAMLESS	51127
	AL 2024-T42 TUBE DRAWN SEAMLESS	51128
	AL 6061-O TUBE DRAWN SEAMLESS	51366
	AL 6061-T42 TUBE DRAWN SEAMLESS	51368
	AL 7075-O TUBE DRAWN	51477
	AL 7075-T6 TUBE DRAWN	51478
	AL 7075-T62 TUBE DRAWN	51479
	AL 7075-T73 TUBE DRAWN	51480
	AL 3003-O TUBE DRAWN SEAMLESS CLAD	51618
	AL 3003-H14 TUBE DRAWN SEAMLESS CLAD	51619
	AL 3003-H18 TUBE DRAWN SEAMLESS CLAD	51620
	AL 3003-H113 TUBE DRAWN SEAMLESS CLAD	51621
	AL 1100-H12 TUBE DRAWN	51985
	AL 1100-H16 TUBE DRAWN	51987
	AL 1100-H18 TUBE DRAWN	51988
	AL 1100-H113 TUBE DRAWN	51989
	AL 2011-T3 TUBE DRAWN SEAMLESS	52006
	AL 2011-T4511 TUBE DRAWN SEAMLESS	52007
	AL 2011-T8 TUBE DRAWN SEAMLESS	52008
	AL 5154-O TUBE DRAWN SEAMLESS	52048
	AL 5154-H34 TUBE DRAWN SEAMLESS	52049
	AL 5154-H38 TUBE DRAWN SEAMLESS	52050
	AL 1060-O TUBE DRAWN	52086
	AL 1060-H12 TUBE DRAWN	52087
	AL 1060-H14 TUBE DRAWN	52088
	AL 1060-H18 TUBE DRAWN	52089
	AL 1060-H113 TUBE DRAWN	52090
	AL 6063-T31 TUBE DRAWN SEAMLESS	52164
	AL 5456-O TUBE DRAWN SEAMLESS	52286
	AL 2014-O TUBE DRAWN SEAMLESS	52409
	AL 2014-T4 TUBE DRAWN SEAMLESS	52410
	AL 2014-T42 TUBE DRAWN SEAMLESS	52411
	AL 2014-T6 TUBE DRAWN SEAMLESS	52412
	AL 2014-T62 TUBE DRAWN SEAMLESS	52413
	AL 1060-O TUBE DRAWN SEAMLESS	52564
	AL 1060-H14 TUBE DRAWN SEAMLESS	52566
	AL 1060-H18 TUBE DRAWN SEAMLESS	52567
	AL 1100-O TUBE DRAWN SEAMLESS	52589
ASTM B210	AL 1100-H12 TUBE DRAWN SEAMLESS	52590
	AL 1100-H16 TUBE DRAWN SEAMLESS	52591
	AL 1100-H18 TUBE DRAWN SEAMLESS	52592
	AL 1100-H113 TUBE DRAWN SEAMLESS	52593
	AL 5050-O TUBE DRAWN SEAMLESS	52594
	AL 5050-H32 TUBE DRAWN SEAMLESS	52595
	AL 5050-H34 TUBE DRAWN SEAMLESS	52596
	AL 5050-H36	52597
	AL 5050-H38 TUBE DRAWN SEAMLESS	52598
	AL 5005-O TUBE DRAWN SEAMLESS	52599
	AL 1100-O TUBE DRAWN	52697
	AL 5052-O TUBE DRAWN SEAMLESS	52795
	AL 5052-H32 TUBE DRAWN SEAMLESS	52796
	AL 5052-H34 TUBE DRAWN SEAMLESS	52797
	AL 5052-H36 TUBE DRAWN SEAMLESS	52798
	AL 5052-H38 TUBE DRAWN SEAMLESS	52799
	AL 6262-T62 TUBE DRAWN SEAMLESS	52859
	AL 6262-T9 TUBE DRAWN SEAMLESS	52860
	AL 6262-T6 TUBE DRAWN SEAMLESS	52861
	AL 6063-O TUBE DRAWN SEAMLESS	52888
	AL 6063-T4 TUBE DRAWN SEAMLESS	52889
	AL 6063-T42 TUBE DRAWN SEAMLESS	52891
	AL 6063-T6 TUBE DRAWN SEAMLESS	52892
	AL 6063-T62 TUBE DRAWN SEAMLESS	52897
	AL 6063-T83 TUBE DRAWN SEAMLESS	52898
	AL 6063-T831 TUBE DRAWN SEAMLESS	52899
	AL 6063-T832 TUBE DRAWN SEAMLESS	52900
	AL 7075-O TUBE DRAWN SEAMLESS	52932
	AL 7075-T6 TUBE DRAWN SEAMLESS	52933
	AL 7075-T62 TUBE DRAWN SEAMLESS	52934
	AL 7075-T73 TUBE DRAWN SEAMLESS	52935
	AL 3003-O TUBE DRAWN SEAMLESS	53002
	AL 3003-H12 TUBE DRAWN SEAMLESS	53003
	AL 3003-H14 TUBE DRAWN SEAMLESS	53004
	AL 3003-H16 TUBE DRAWN SEAMLESS	53005
	AL 3003-H18 TUBE DRAWN SEAMLESS	53006
	AL 3003-H113 TUBE DRAWN SEAMLESS	53007
ASTM B211	AL 6061-T4 BAR ROLLED	10019
	AL 6061-T6 BAR ROLLED	10023
	AL 7075-T7351 BAR ROLLED	10047
	AL 2024-T6 ROD ROLLED	10292
	AL 5056-O ROD ROLLED	10443
	AL 2024-T851 BAR ROLLED	10508
	AL 2024-O ROD ROLLED	10525
	AL 2024-O BAR ROLLED	10744
	AL 2017-O BAR ROLLED	30099
	AL 3003-H112 BAR ROLLED	50130
	AL 2014-T6 BAR COLD FINISHED	50220
	AL 2024-T6 BAR COLD FINISHED	50221
	AL 2017-T451 BAR ROLLED	50253
	AL 2017-T42 BAR ROLLED	50254
	AL 2017-T4 BAR ROLLED	50255
	AL 2024-T4 BAR ROLLED	50267
	AL 5056-O BAR ROLLED	50275
	AL 2017-T4 ROD ROLLED	50543

MSFC-HDBK-527 REV F ■ 9999942 0005045 1 ■

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
ASTM B211	AL 2017-T4 WIRE ROLLED	50544
	AL 2017-T42 ROD ROLLED	50545
	AL 2017-T42 WIRE ROLLED	50546
	AL 2017-T451 ROD ROLLED	50547
	AL 2017-O ROD ROLLED	50549
	AL 2017-O WIRE ROLLED	50550
	AL 2024-T4 ROD ROLLED	50560
	AL 2024-T4 WIRE ROLLED	50561
	AL 2024-T6 WIRE COLD FINISHED	50566
	AL 2024-O WIRE ROLLED	50580
	AL 3003-H112 ROD ROLLED	50597
	AL 3003-O WIRE ROLLED	50598
	AL 5056-O WIRE ROLLED	50615
	AL 6061-O ROD DRAWN	50632
	AL 6061-T4 WIRE COLD FINISHED	50633
	AL 6061-T4 ROD ROLLED	50640
	AL 6061-T6 ROD ROLLED	50651
	AL 6061-O ROD ROLLED	50652
	AL 7075-O WIRE ROLLED	50674
	AL 2219-T851 BAR ROLLED	51048
	AL 2219-T851 ROD ROLLED	51049
	AL 2024-T6 BAR ROLLED	51098
	AL 2024-T42 WIRE ROLLED	51099
	AL 2024-T42 ROD ROLLED	51100
	AL 2024-T42 BAR ROLLED	51101
	AL 2024-T62 WIRE ROLLED	51102
	AL 2024-T62 ROD ROLLED	51103
	AL 2024-T62 BAR ROLLED	51104
	AL 2024-T36 WIRE ROLLED	51105
	AL 2024-T351 BAR ROLLED	51106
	AL 2024-T351 ROD ROLLED	51107
	AL 2024-T851 ROD ROLLED	51108
	AL 5056-H111 WIRE ROLLED	51214
	AL 5056-H12 WIRE ROLLED	51215
	AL 5056-H32 WIRE ROLLED	51216
	AL 5056-H14 WIRE ROLLED	51217
	AL 5056-H34 WIRE ROLLED	51218
	AL 5056-H18 WIRE ROLLED	51219
	AL 5056-H38 WIRE ROLLED	51220
	AL 5056-H192 WIRE ROLLED	51221
	AL 5056-H392 WIRE ROLLED	51222
	AL 6061-T451 WIRE	51255
	AL 6061-T94 WIRE	51256
	AL 6061-T651 WIRE	51257
	AL 6061-T89 WIRE	51258
	AL 6061-T42 BAR ROLLED	51294
	AL 6061-T62 BAR ROLLED	51295
	AL 6061-T6 BAR COLD FINISHED	51298
	AL 6061-T651 BAR COLD FINISHED	51299
	AL 6061-T42 ROD ROLLED	51300
	AL 6061-T62 ROD ROLLED	51301
	AL 6061-T6 ROD COLD FINISHED	51305
	AL 6061-T62 ROD COLD FINISHED	51306
	AL 6061-T651 ROD COLD FINISHED	51307
	AL 6061-T4 WIRE ROLLED	51308
ASTM B211	AL 6061-T42 WIRE ROLLED	51309
	AL 6061-T6 WIRE ROLLED	51310
	AL 6061-T62 WIRE	51311
	AL 7075-O BAR ROLLED	51385
	AL 7075-O BAR COLD FINISHED	51386
	AL 7075-T6 WIRE ROLLED	51387
	AL 7075-T6 WIRE COLD FINISHED	51388
	AL 7075-T6 ROD ROLLED	51389
	AL 7075-T6 ROD COLD FINISHED	51390
	AL 7075-T6 BAR ROLLED	51391
	AL 7075-T6 BAR COLD FINISHED	51392
	AL 7075-T62 WIRE ROLLED	51393
	AL 7075-T62 WIRE COLD FINISHED	51394
	AL 7075-T62 ROD ROLLED	51395
	AL 7075-T62 ROD COLD FINISHED	51396
	AL 7075-T62 BAR ROLLED	51397
	AL 7075-T62 BAR COLD FINISHED	51398
	AL 7075-T651 WIRE ROLLED	51399
	AL 7075-T651 WIRE COLD FINISHED	51400
	AL 7075-T651 ROD ROLLED	51401
	AL 7075-T651 ROD COLD FINISHED	51402
	AL 7075-T651 BAR ROLLED	51403
	AL 7075-T651 BAR COLD FINISHED	51404
	AL 7075-T73 WIRE ROLLED	51405
	AL 7075-T73 WIRE COLD FINISHED	51406
	AL 7075-T73 ROD ROLLED	51407
	AL 7075-T73 ROD COLD FINISHED	51408
	AL 7075-T73 BAR ROLLED	51409
	AL 7075-T73 BAR COLD FINISHED	51410
	AL 7075-T7351 WIRE ROLLED	51411
	AL 7075-T7351 WIRE COLD FINISHED	51412
	AL 7075-T7351 ROD ROLLED	51413
	AL 7075-T7351 ROD COLD FINISHED	51414
	AL 7075-T7351 BAR COLD FINISHED	51415
	AL 2014-O BAR ROLLED	51520
	AL 2014-T4 BAR ROLLED	51521
	AL 2014-T42 BAR ROLLED	51522
	AL 2014-T451 BAR ROLLED	51523
	AL 2014-T62 BAR ROLLED	51524
	AL 2014-T651 BAR ROLLED	51525
	AL 2014-O BAR COLD FINISHED	51527
	AL 2014-T4 BAR COLD FINISHED	51528
	AL 2014-T42 BAR COLD FINISHED	51529
	AL 2014-T451 BAR COLD FINISHED	51531
	AL 2014-T62 BAR COLD FINISHED	51532
	AL 2014-T651 BAR COLD FINISHED	51533
	AL 5056-H192 WIRE ROLLED CLAD	51570
	AL 5056-H392 WIRE ROLLED CLAD	51572
	AL 5056-H393 WIRE ROLLED CLAD	51571
	AL 6066-T6510 ROD EXTRUDED	51854
	AL 5052-O WIRE ROLLED	51911
	AL 5052-O ROD ROLLED	51912
	AL 5052-O BAR ROLLED	51913
	AL 5052-H32 WIRE ROLLED	51914
	AL 5052-H34 WIRE ROLLED	51915

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005046 3

SPECIFICATION	DESIGNATION	MATCD
ASTM B211	AL 5052-H36 WIRE ROLLED	51916
	AL 5052-H38 WIRE ROLLED	51917
	AL 5052-F ROD ROLLED	51918
	AL 5052-F BAR ROLLED	51919
	AL 1100-O WIRE ROLLED	51962
	AL 1100-O ROD ROLLED	51963
	AL 1100-O BAR ROLLED	51964
	AL 1100-H12 WIRE ROLLED	51965
	AL 1100-H14 WIRE ROLLED	51966
	AL 1100-H16 WIRE ROLLED	51967
	AL 1100-H18 WIRE ROLLED	51968
	AL 1100-H112 WIRE ROLLED	51969
	AL 1100-H112 ROD ROLLED	51970
	AL 1100-H112 BAR ROLLED	51971
	AL 2011-T3 ROD ROLLED	52009
	AL 2011-T4 ROD ROLLED	52010
	AL 2011-T451 ROD ROLLED	52011
	AL 2011-T8 ROD ROLLED	52012
	AL 2011-T3 BAR ROLLED	52013
	AL 2011-T4 BAR ROLLED	52014
	AL 2011-T451 BAR ROLLED	52015
	AL 2011-T8 BAR ROLLED	52016
	AL 2011-T3 WIRE ROLLED	52017
	AL 2011-T8 WIRE ROLLED	52018
	AL 5154-O ROD ROLLED	52028
	AL 5154-H112 ROD ROLLED	52029
	AL 5154-O BAR ROLLED	52030
	AL 5154-H112 BAR ROLLED	52031
	AL 5154-O WIRE ROLLED	52032
	AL 5154-H112 WIRE ROLLED	52033
	AL 5154-H32 WIRE ROLLED	52034
	AL 5154-H34 WIRE ROLLED	52035
	AL 5154-H36 WIRE ROLLED	52036
	AL 5154-H38 WIRE ROLLED	52037
	AL 1060-O WIRE ROLLED	52067
	AL 1060-H14 WIRE ROLLED	52068
	AL 1060-H18 WIRE ROLLED	52069
	AL 1060-O ROD ROLLED	52070
	AL 1060-H14 ROD ROLLED	52071
	AL 1060-H18 ROD ROLLED	52072
	AL 1060-O BAR ROLLED	52073
	AL 1060-H14 BAR ROLLED	52074
	AL 1060-H18 BAR ROLLED	52075
	AL 6262-T6 WIRE ROLLED	52229
	AL 6262-T6 ROD ROLLED	52230
	AL 6262-T6 BAR ROLLED	52231
	AL 6262-T651 WIRE ROLLED	52232
	AL 6262-T651 ROD ROLLED	52233
	AL 6262-T651 BAR ROLLED	52234
	AL 6262-T9 WIRE ROLLED	52235
	AL 6262-T9 ROD ROLLED	52236
	AL 6262-T9 BAR ROLLED	52237
	AL 6262-T6 ROD EXTRUDED	52239
	AL 2014-O ROD ROLLED	52306
	AL 2014-T4 ROD ROLLED	52307

SPECIFICATION	DESIGNATION	MATCD
ASTM B211	AL 2014-T42 ROD ROLLED	52308
	AL 2014-T451 ROD ROLLED	52309
	AL 2014-T6 ROD ROLLED	52310
	AL 2014-T62 ROD ROLLED	52311
	AL 2014-T651 ROD ROLLED	52312
	AL 2014-O ROD COLD FINISHED	52313
	AL 2014-T4 ROD COLD FINISHED	52314
	AL 2014-T42 ROD COLD FINISHED	52315
	AL 2014-T451 ROD COLD FINISHED	52316
	AL 2014-T6 ROD COLD FINISHED	52317
	AL 2014-T62 ROD COLD FINISHED	52318
	AL 2014-T651 ROD COLD FINISHED	52319
	AL 2014-O WIRE ROLLED	52320
	AL 2014-T4 WIRE ROLLED	52321
	AL 2014-T42 WIRE ROLLED	52322
	AL 2014-T451 WIRE ROLLED	52323
	AL 2014-T6 WIRE ROLLED	52324
	AL 2014-T62 WIRE ROLLED	52325
	AL 2014-T651 WIRE ROLLED	52326
	AL 2014-O WIRE COLD FINISHED	52327
	AL 2014-T4 WIRE COLD FINISHED	52328
	AL 2014-T42 WIRE COLD FINISHED	52329
	AL 2014-T451 WIRE COLD FINISHED	52330
	AL 2014-T6 WIRE COLD FINISHED	52331
	AL 2014-T62 WIRE COLD FINISHED	52332
	AL 2014-T651 WIRE COLD FINISHED	52333
	AL 2011-T3 ROD COLD FINISHED	52540
	AL 2011-T4 ROD COLD FINISHED	52541
	AL 2011-T8 ROD COLD FINISHED	52543
	AL 2011-T3 BAR COLD FINISHED	52544
	AL 2011-T4 BAR COLD FINISHED	52545
	AL 2011-T451 BAR COLD FINISHED	52546
	AL 2011-T8 BAR COLD FINISHED	52547
	AL 2011-T3 WIRE COLD FINISHED	52548
	AL 2011-T8 WIRE COLD FINISHED	52549
	AL 2011-T4 WIRE ROLLED	52550
	AL 2011-T451 WIRE ROLLED	52551
	AL 2011-T4 WIRE COLD FINISHED	52552
	AL 2011-T451 WIRE COLD FINISHED	52553
	AL 1060-O WIRE COLD FINISHED	52554
	AL 1060-H14 WIRE COLD FINISHED	52555
	AL 1060-H18 WIRE COLD FINISHED	52556
	AL 1060-O ROD COLD FINISHED	52557
	AL 1060-H18 ROD COLD FINISHED	52559
	AL 1060-O BAR COLD FINISHED	52560
	AL 1060-H18 BAR COLD FINISHED	52562
	AL 1100-O WIRE COLD FINISHED	52573
	AL 1100-O ROD COLD FINISHED	52574
	AL 1100-O BAR COLD FINISHED	52575
	AL 1100-H12 WIRE COLD FINISHED	52576
	AL 1100-H14 WIRE COLD FINISHED	52577
	AL 1100-H16 WIRE COLD FINISHED	52578
	AL 1100-H18 WIRE COLD FINISHED	52579
	AL 1100-H112 WIRE COLD FINISHED	52580
	AL 1100-H112 ROD COLD FINISHED	52581

MSFC-HDBK-527 REV F 9999942 0005047 5

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
ASTM B211	AL 1100-H112 BAR COLD FINISHED	52582
	AL 2219-T851 BAR COLD FINISHED	52600
	AL 2219-T851 ROD COLD FINISHED	52601
	AL 5052-O WIRE COLD FINISHED	52785
	AL 5052-O ROD COLD FINISHED	52786
	AL 5052-O BAR COLD FINISHED	52787
	AL 5052-H32 WIRE COLD FINISHED	52788
	AL 5052-H34 WIRE COLD FINISHED	52789
	AL 5052-H36 WIRE COLD FINISHED	52790
	AL 5052-H38 WIRE COLD FINISHED	52791
	AL 5052-F ROD COLD FINISHED	52792
	AL 5052-F BAR COLD FINISHED	52793
	AL 2017-T451 WIRE ROLLED	52831
	AL 5154-O ROD COLD FINISHED	52839
	AL 5154-H112 ROD COLD FINISHED	52840
	AL 5154-O BAR COLD FINISHED	52841
	AL 5154-H112 BAR COLD FINISHED	52842
	AL 5154-O WIRE COLD FINISHED	52843
	AL 5154-H112 WIRE COLD FINISHED	52844
	AL 5154-H32 WIRE COLD FINISHED	52845
	AL 5154-H34 WIRE COLD FINISHED	52846
	AL 5154-H36 WIRE COLD FINISHED	52847
	AL 5154-H38 WIRE COLD FINISHED	52848
	AL 6262-T6 WIRE COLD FINISHED	52850
	AL 6262-T6 ROD COLD FINISHED	52851
	AL 6262-T6 BAR COLD FINISHED	52852
	AL 6262-T651 WIRE COLD FINISHED	52853
	AL 6262-T651 ROD COLD FINISHED	52854
	AL 6262-T651 BAR COLD FINISHED	52855
	AL 6262-T9 WIRE COLD FINISHED	52856
	AL 6262-T9 ROD COLD FINISHED	52857
	AL 6062-T9 BAR COLD FINISHED	52858
	AL 5056-H192 WIRE COLD FINISHED CLAD	52878
	AL 5056-H392 WIRE COLD FINISHED CLAD	52879
	AL 5056-H393 WIRE COLD FINISHED CLAD	52880
	AL 7075-O WIRE COLD FINISHED	52911
	AL 7075-O ROD ROLLED	52912
	AL 7075-O ROD COLD FINISHED	52913
	AL 3003-O WIRE COLD FINISHED	52968
	AL 3003-O ROD ROLLED	52969
	AL 3003-O ROD COLD FINISHED	52970
	AL 3003-O BAR ROLLED	52971
	AL 3003-O BAR COLD FINISHED	52972
	AL 3003-H12 WIRE ROLLED	52973
	AL 3003-H12 WIRE COLD FINISHED	52974
	AL 3003-H14 WIRE ROLLED	52975
	AL 3003-H14 WIRE COLD FINISHED	52976
	AL 3003-H16 WIRE ROLLED	52977
	AL 3003-H16 WIRE COLD FINISHED	52978
	AL 3003-H18 WIRE ROLLED	52979
	AL 3003-H18 WIRE COLD FINISHED	52980
	AL 3003-H112 WIRE ROLLED	52981
	AL 3003-H112 WIRE COLD FINISHED	52982
	AL 3003-H112 ROD COLD FINISHED	52983
	AL 3003-H112 BAR COLD FINISHED	52984

SPECIFICATION	DESIGNATION	MATCD
ASTM B211	AL 2014-T6 BAR ROLLED	53028
	AL 2024-O BAR COLD FINISHED	53029
	AL 2024-O ROD COLD FINISHED	53032
	AL 2024-O WIRE COLD FINISHED	53033
	AL 2024-T351 BAR COLD FINISHED	53037
	AL 2024-T351 ROD COLD FINISHED	53038
	AL 2024-T36 WIRE COLD FINISHED	53045
	AL 2024-T4 BAR COLD FINISHED	53046
	AL 2024-T4 ROD COLD FINISHED	53047
	AL 2024-T4 WIRE COLD FINISHED	53048
	AL 2024-T42 BAR COLD FINISHED	53050
	AL 2024-T42 ROD COLD FINISHED	53051
	AL 2024-T42 WIRE COLD FINISHED	53052
	AL 2024-T6 ROD COLD FINISHED	53053
	AL 2024-T6 WIRE ROLLED	53054
	AL 2024-T62 BAR COLD FINISHED	53055
	AL 2024-T62 ROD COLD FINISHED	53056
	AL 2024-T62 WIRE COLD FINISHED	53057
	AL 2024-T851 ROD COLD FINISHED	53063
	AL 2024-T851 BAR COLD FINISHED	53064
ASTM B221	AL 2219-T8511 BAR EXTRUDED	10013
	AL 6061-T4511 BAR EXTRUDED	10020
	AL 6061-T6 BAR EXTRUDED	10024
	AL 2219-T62 BAR EXTRUDED	10036
	AL 5456-H111 BAR EXTRUDED	10253
	AL 5456-H112 BAR EXTRUDED	10254
	AL 3003-O ROD EXTRUDED	10385
	AL 6063-T42 BAR EXTRUDED	10394
	AL 2219-T62 TUBE	10412
	AL 2024-T8510 BAR EXTRUDED	10420
	AL 7075-T73511 BAR EXTRUDED	10421
	AL 3003-O TUBE EXTRUDED	10437
	AL 6061-T4 TUBE	10732
	AL 2024-T3 BAR EXTRUDED	30112
	AL 7075-T62 BAR EXTRUDED	30122
	AL 2219-T3511 BAR EXTRUDED	50088
	AL 6063-T52 BAR EXTRUDED	50279
	AL 7005-T53 BAR EXTRUDED	50291
	AL 6061-T6511 BAR EXTRUDED	50299
	AL 7075-T73 TUBE EXTRUDED	50509
	AL 2219-T81 TUBE	50517
	AL 2024-T3 ROD EXTRUDED	50552
	AL 2024-T3 WIRE EXTRUDED	50553
	AL 2024-T8510 ROD EXTRUDED	50577
	AL 2024-T8510 WIRE EXTRUDED	50578
	AL 2219-T3511 ROD EXTRUDED	50585
	AL 2219-T3511 WIRE EXTRUDED	50586
	AL 2219-T8511 ROD EXTRUDED	50593
	AL 2219-T8511 SHAPES EXTRUDED	50594
	AL 3003-O BAR EXTRUDED	50602
	AL 3003-O WIRE EXTRUDED	50603
	AL 5456-H111 ROD EXTRUDED	50619
	AL 5456-H111 WIRE EXTRUDED	50620
	AL 5456-H112 ROD EXTRUDED	50621
	AL 5456-H112 WIRE EXTRUDED	50622

MSFC-HDBK-527 REV F 9999942 0005048 7

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
ASTM B221	AL 6061-T4511 ROD EXTRUDED	50638
	AL 6061-T4511 WIRE EXTRUDED	50639
	AL 6061-T6 ROD EXTRUDED	50643
	AL 6061-T6 WIRE EXTRUDED	50644
	AL 6061-T6511 ROD EXTRUDED	50648
	AL 6061-T6511 WIRE EXTRUDED	50649
	AL 6061-O WIRE EXTRUDED	50653
	AL 6063-T42 ROD EXTRUDED	50655
	AL 6063-T42 WIRE EXTRUDED	50656
	AL 6063-T52 ROD EXTRUDED	50657
	AL 6063-T52 WIRE EXTRUDED	50658
	AL 7075-T62 WIRE EXTRUDED	50665
	AL 7075-T73511 ROD EXTRUDED	50666
	AL 7075-T73511 WIRE EXTRUDED	50667
	AL 6063-T6 BAR EXTRUDED	50970
	AL 7005-T53 SHAPES EXTRUDED	50987
	AL 7005-T53 TUBE EXTRUDED	50988
	AL 5086-O WIRE EXTRUDED	51005
	AL 5086-O ROD EXTRUDED	51006
	AL 5086-O BAR EXTRUDED	51007
	AL 5086-O SHAPES EXTRUDED	51008
	AL 5086-O TUBE EXTRUDED	51009
	AL 5086-H111 WIRE EXTRUDED	51010
	AL 5086-H111 ROD EXTRUDED	51011
	AL 5086-H111 BAR EXTRUDED	51012
	AL 5086-H111 SHAPES EXTRUDED	51013
	AL 5086-H111 TUBE EXTRUDED	51014
	AL 5086-H112 WIRE EXTRUDED	51015
	AL 5086-H112 ROD EXTRUDED	51016
	AL 5086-H112 BAR EXTRUDED	51017
	AL 5086-H112 SHAPES EXTRUDED	51018
	AL 5086-H112 TUBE EXTRUDED	51019
	AL 2219-O WIRE EXTRUDED	51050
	AL 2219-O ROD EXTRUDED	51051
	AL 2219-O BAR EXTRUDED	51052
	AL 2219-O SHAPES EXTRUDED	51053
	AL 2219-O TUBE EXTRUDED	51054
	AL 2219-T31 WIRE EXTRUDED	51055
	AL 2219-T31 ROD EXTRUDED	51056
	AL 2219-T31 BAR EXTRUDED	51057
	AL 2219-T31 SHAPES EXTRUDED	51058
	AL 2219-T31 TUBE EXTRUDED	51059
	AL 2219-T3510 WIRE EXTRUDED	51060
	AL 2219-T3510 ROD EXTRUDED	51061
	AL 2219-T3510 BAR EXTRUDED	51062
	AL 2219-T3510 SHAPES EXTRUDED	51063
	AL 2219-T3510 TUBE EXTRUDED	51064
	AL 2219-T3511 SHAPES EXTRUDED	51066
	AL 2219-T3511 TUBE EXTRUDED	51067
	AL 2219-T81 WIRE EXTRUDED	51068
	AL 2219-T81 ROD EXTRUDED	51069
	AL 2219-T81 BAR EXTRUDED	51070
	AL 2219-T81 SHAPES EXTRUDED	51071
	AL 2219-T8510 WIRE EXTRUDED	51072
	AL 2219-T8510 ROD EXTRUDED	51073
ASTM B221	AL 2219-T8510 BAR EXTRUDED	51074
	AL 2219-T8510 SHAPES EXTRUDED	51075
	AL 2219-T8510 TUBE EXTRUDED	51076
	AL 2219-T8511 WIRE EXTRUDED	51077
	AL 2219-T8511 TUBE EXTRUDED	51079
	AL 2024-O WIRE EXTRUDED	51109
	AL 2024-T42 WIRE EXTRUDED	51110
	AL 2024-T81 WIRE EXTRUDED	51111
	AL 2024-O BAR EXTRUDED	51112
	AL 2024-T3510 BAR EXTRUDED	51113
	AL 2024-T3511 BAR EXTRUDED	51114
	AL 2024-T42 BAR EXTRUDED	51115
	AL 2024-O TUBE EXTRUDED	51117
	AL 2024-T3 TUBE EXTRUDED	51118
	AL 2024-T3510 TUBE EXTRUDED	51120
	AL 2024-T3511 TUBE EXTRUDED	51121
	AL 2024-T42 TUBE EXTRUDED	51122
	AL 2024-T81 TUBE EXTRUDED	51123
	AL 2024-T8510 TUBE EXTRUDED	51124
	AL 2024-T8511 TUBE EXTRUDED	51125
	AL 2024-O ROD EXTRUDED	51148
	AL 2024-T3510 ROD EXTRUDED	51150
	AL 2024-T3511 ROD EXTRUDED	51151
	AL 2024-T42 ROD EXTRUDED	51152
	AL 2024-T8511 ROD EXTRUDED	51153
	AL 2024-O SHAPES EXTRUDED	51155
	AL 2024-T3 SHAPES EXTRUDED	51156
	AL 2024-T3510 SHAPES EXTRUDED	51157
	AL 2024-T3511 SHAPES EXTRUDED	51158
	AL 2024-T42 SHAPES EXTRUDED	51159
	AL 2024-T8511 SHAPES EXTRUDED	51160
	AL 6061-T62 ROD EXTRUDED	51259
	AL 6061-T62 BAR EXTRUDED	51260
	AL 6061-T4510 ROD EXTRUDED	51320
	AL 6061-T42 ROD EXTRUDED	51321
	AL 6061-T1 ROD EXTRUDED	51323
	AL 6061-T51 ROD EXTRUDED	51324
	AL 6061-T6510 ROD EXTRUDED	51325
	AL 6061-T1 BAR EXTRUDED	51326
	AL 6061-T4510 BAR EXTRUDED	51327
	AL 6061-T42 BAR EXTRUDED	51328
	AL 6061-T51 BAR EXTRUDED	51329
	AL 6061-T6510 BAR EXTRUDED	51330
	AL 6061-O SHAPES EXTRUDED	51331
	AL 6061-T6 SHAPES EXTRUDED	51332
	AL 6061-T62 SHAPES EXTRUDED	51333
	AL 6061-T1 SHAPES EXTRUDED	51334
	AL 6061-T4510 SHAPES EXTRUDED	51335
	AL 6061-T4511 SHAPES EXTRUDED	51336
	AL 6061-T42 SHAPES EXTRUDED	51337
	AL 6061-T51 SHAPES EXTRUDED	51338
	AL 6061-T6510 SHAPES EXTRUDED	51339
	AL 6061-T6511 SHAPES EXTRUDED	51340
	AL 6061-O TUBE EXTRUDED	51341
	AL 6061-T1 TUBE EXTRUDED	51342

MSFC-HDBK-527 REV F 9999942 0005049 9

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
ASTM B221	AL 6061-T4510 TUBE EXTRUDED	51343
	AL 6061-T4511 TUBE EXTRUDED	51344
	AL 6061-T42 TUBE EXTRUDED	51345
	AL 6061-T51 TUBE EXTRUDED	51346
	AL 6061-T6510 TUBE EXTRUDED	51347
	AL 6061-T6511 TUBE EXTRUDED	51348
	AL 6061-T6 TUBE EXTRUDED	51349
	AL 6061-T62 TUBE EXTRUDED	51350
	AL 6061-T1 WIRE EXTRUDED	51351
	AL 6061-T4 WIRE EXTRUDED	51352
	AL 6061-T4510 WIRE EXTRUDED	51353
	AL 6061-T42 WIRE EXTRUDED	51354
	AL 6061-T51 WIRE EXTRUDED	51355
	AL 6061-T62 WIRE EXTRUDED	51356
	AL 6061-T6510 WIRE EXTRUDED	51357
	AL 7075-T73 WIRE EXTRUDED	51431
	AL 7075-T73 ROD EXTRUDED	51432
	AL 7075-T73 BAR EXTRUDED	51433
	AL 7075-T73 SHAPES EXTRUDED	51434
	AL 7075-T73510 WIRE EXTRUDED	51435
	AL 7075-T73510 ROD EXTRUDED	51436
	AL 7075-T73510 BAR EXTRUDED	51437
	AL 7075-T73510 SHAPES EXTRUDED	51438
	AL 7075-T73510 TUBE EXTRUDED	51439
	AL 7075-T73511 SHAPES EXTRUDED	51440
	AL 7075-T76 WIRE EXTRUDED	51441
	AL 7075-T76 ROD EXTRUDED	51442
	AL 7075-T76 BAR EXTRUDED	51443
	AL 7075-T76 SHAPES EXTRUDED	51444
	AL 7075-T76 TUBE EXTRUDED	51445
	AL 7075-T76510 WIRE EXTRUDED	51446
	AL 7075-T76510 BAR EXTRUDED	51448
	AL 7075-T76510 SHAPES EXTRUDED	51449
	AL 7075-T76510 TUBE EXTRUDED	51450
	AL 7075-T76511 WIRE EXTRUDED	51451
	AL 7075-T76511 ROD EXTRUDED	51452
	AL 7075-T76511 BAR EXTRUDED	51453
	AL 7075-T76511 SHAPES EXTRUDED	51454
	AL 7075-T76511 TUBE EXTRUDED	51455
	AL 7075-O BAR EXTRUDED	51456
	AL 7075-O SHAPES EXTRUDED	51457
	AL 7075-O TUBE EXTRUDED	51458
	AL 7075-T6 WIRE EXTRUDED	51459
	AL 7075-T6 ROD EXTRUDED	51460
	AL 7075-T6 BAR EXTRUDED	51461
	AL 7075-T6 SHAPES EXTRUDED	51462
	AL 7075-T6 TUBE EXTRUDED	51463
	AL 7075-T62 ROD EXTRUDED	51464
	AL 7075-T62 SHAPES EXTRUDED	51465
	AL 7075-T62 TUBE EXTRUDED	51466
	AL 7075-T6510 WIRE EXTRUDED	51467
	AL 7075-T6510 ROD EXTRUDED	51468
	AL 7075-T6510 BAR EXTRUDED	51469
	AL 7075-T6510 SHAPES EXTRUDED	51470
	AL 7075-T6510 TUBE EXTRUDED	51471
ASTM B221	AL 7075-T6511 WIRE EXTRUDED	51472
	AL 7075-T6511 ROD EXTRUDED	51473
	AL 7075-T6511 BAR EXTRUDED	51474
	AL 7075-T6511 SHAPES EXTRUDED	51475
	AL 7075-T6511 TUBE EXTRUDED	51476
	AL 6463-T1 WIRE EXTRUDED	51575
	AL 6463-T1 ROD EXTRUDED	51576
	AL 6463-T1 BAR EXTRUDED	51577
	AL 6463-T1 SHAPES EXTRUDED	51578
	AL 6463-T1 TUBE EXTRUDED	51579
	AL 6463-T5 WIRE EXTRUDED	51580
	AL 6463-T5 ROD EXTRUDED	51581
	AL 6463-T5 BAR EXTRUDED	51582
	AL 6463-T5 SHAPES EXTRUDED	51583
	AL 6563-T5 TUBE EXTRUDED	51584
	AL 6463-T6 WIRE EXTRUDED	51585
	AL 6463-T6 ROD EXTRUDED	51586
	AL 6463-T6 BAR EXTRUDED	51587
	AL 6463-T6 SHAPES EXTRUDED	51588
	AL 6463-T6 TUBE EXTRUDED	51589
	AL 3004-O TUBE EXTRUDED	51603
	AL 3003-O TUBE EXTRUDED CLAD	51622
	AL 3003-H112 TUBE EXTRUDED CLAD	51623
	AL 6005-T1 WIRE EXTRUDED	51738
	AL 6005-T5 WIRE EXTRUDED	51739
	AL 6005-T1 ROD EXTRUDED	51740
	AL 6005-T5 ROD EXTRUDED	51741
	AL 6005-T1 BAR EXTRUDED	51742
	AL 6005-T5 BAR EXTRUDED	51743
	AL 6005-T1 SHAPES EXTRUDED	51744
	AL 6005-T5 SHAPES EXTRUDED	51745
	AL 6005-T1 TUBE EXTRUDED	51746
	AL 6005-T5 TUBE EXTRUDED	51747
	AL 6351-T54 WIRE EXTRUDED	51779
	AL 6351-T54 ROD EXTRUDED	51780
	AL 6351-T54 BAR EXTRUDED	51781
	AL 6351-T54 SHAPES EXTRUDED	51782
	AL 6351-T54 TUBE EXTRUDED	51783
	AL 6066-O WIRE EXTRUDED	51839
	AL 6066-T4 WIRE EXTRUDED	51840
	AL 6066-T4510 WIRE EXTRUDED	51841
	AL 6066-T4511 WIRE EXTRUDED	51842
	AL 6066-T42 WIRE EXTRUDED	51843
	AL 6066-T6 WIRE EXTRUDED	51844
	AL 6066-T6510 WIRE EXTRUDED	51845
	AL 6066-T6511 WIRE EXTRUDED	51846
	AL 6066-T62 WIRE EXTRUDED	51847
	AL 6066-O ROD EXTRUDED	51848
	AL 6066-T4 ROD EXTRUDED	51849
	AL 6066-T4510 ROD EXTRUDED	51850
	AL 6066-T4511 ROD EXTRUDED	51851
	AL 6066-T42 ROD EXTRUDED	51852
	AL 6066-T6 ROD EXTRUDED	51853
	AL 6066-T6511 ROD EXTRUDED	51855
	AL 6066-T62 ROD EXTRUDED	51856

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005050 5

SPECIFICATION	DESIGNATION	MATCD
ASTM B221	AL 6066-O BAR EXTRUDED	51857
	AL 6066-T4 BAR EXTRUDED	51858
	AL 6066-T4510 BAR EXTRUDED	51859
	AL 6066-T4511 BAR EXTRUDED	51860
	AL 6066-T42 BAR EXTRUDED	51861
	AL 6066-T6 BAR EXTRUDED	51862
	AL 6066-T6510 BAR EXTRUDED	51863
	AL 6066-T6511 BAR EXTRUDED	51864
	AL 6066-T62 BAR EXTRUDED	51865
	AL 6066-O SHAPES EXTRUDED	51866
	AL 6066-T4 SHAPES EXTRUDED	51867
	AL 6066-T4510 SHAPES EXTRUDED	51868
	AL 6066-T4511 SHAPES EXTRUDED	51869
	AL 6066-T42 SHAPES EXTRUDED	51870
	AL 6066-T6 SHAPES EXTRUDED	51871
	AL 6066-T6510 SHAPES EXTRUDED	51872
	AL 6066-T6511 SHAPES EXTRUDED	51873
	AL 6066-T62 SHAPES EXTRUDED	51874
	AL 6066-O TUBE EXTRUDED	51875
	AL 6066-T4 TUBE EXTRUDED	51876
	AL 6066-T4510 TUBE EXTRUDED	51877
	AL 6066-T4511 TUBE EXTRUDED	51878
	AL 6066-T42 TUBE EXTRUDED	51879
	AL 6066-T6 TUBE EXTRUDED	51880
	AL 6066-T6510 TUBE EXTRUDED	51881
	AL 6066-T6511 TUBE EXTRUDED	51882
	AL 6066-T62 TUBE EXTRUDED	51883
	AL 5454-O WIRE EXTRUDED	51892
	AL 5454-O ROD EXTRUDED	51893
	AL 5454-O BAR EXTRUDED	51894
	AL 5454-O SHAPES EXTRUDED	51895
	AL 5454-O TUBE EXTRUDED	51896
	AL 5454-H111 WIRE EXTRUDED	51897
	AL 5454-H111 ROD EXTRUDED	51898
	AL 5454-H111 BAR EXTRUDED	51899
	AL 5454-H111 SHAPES EXTRUDED	51900
	AL 5454-H111 TUBE EXTRUDED	51901
	AL 5454-H112 WIRE EXTRUDED	51902
	AL 5454-H112 ROD EXTRUDED	51903
	AL 5454-H112 BAR EXTRUDED	51904
	AL 5454-H112 SHAPES EXTRUDED	51905
	AL 5454-H112 TUBE EXTRUDED	51906
	AL 5052-O TUBE EXTRUDED	51941
	AL 1100-O BAR EXTRUDED	51975
	AL 1100-H112 BAR EXTRUDED	51976
	AL 1100-O ROD EXTRUDED	51977
	AL 1100-H112 ROD EXTRUDED	51978
	AL 1100-O WIRE EXTRUDED	51979
	AL 1100-H112 WIRE EXTRUDED	51980
	AL 1100-O SHAPES EXTRUDED	51981
	AL 1100-H112 SHAPES EXTRUDED	51982
	AL 1100-O TUBE EXTRUDED	51983
	AL 1100-H112 TUBE EXTRUDED	51984
	AL 5154-O WIRE EXTRUDED	52038
	AL 5154-H112 WIRE EXTRUDED	52039

SPECIFICATION	DESIGNATION	MATCD
ASTM B221	AL 5154-O ROD EXTRUDED	52040
	AL 5154-H112 ROD EXTRUDED	52041
	AL 5154-O BAR EXTRUDED	52042
	AL 5154-H112 BAR EXTRUDED	52043
	AL 5154-O SHAPES EXTRUDED	52044
	AL 5154-H112 SHAPES EXTRUDED	52045
	AL 5154-O TUBE EXTRUDED	52046
	AL 5154-H112 TUBE EXTRUDED	52047
	AL 1060-O TUBE EXTRUDED	52076
	AL 1060-H112 TUBE EXTRUDED	52077
	AL 1060-O SHAPES EXTRUDED	52078
	AL 1060-H112 SHAPES EXTRUDED	52079
	AL 1060-O BAR EXTRUDED	52080
	AL 1060-H112 BAR EXTRUDED	52081
	AL 1060-O ROD EXTRUDED	52082
	AL 1060-H112 ROD EXTRUDED	52083
	AL 1060-O WIRE EXTRUDED	52084
	AL 1060-H112 WIRE EXTRUDED	52085
	AL 1060-H14 TUBE CONDENSER	52091
	AL 6063-O WIRE EXTRUDED	52124
	AL 6063-O ROD EXTRUDED	52125
	AL 6063-O BAR EXTRUDED	52126
	AL 6063-O SHAPES EXTRUDED	52127
	AL 6063-O TUBE EXTRUDED	52128
	AL 6063-T5 WIRE EXTRUDED	52129
	AL 6063-T5 ROD EXTRUDED	52130
	AL 6063-T5 BAR EXTRUDED	52131
	AL 6063-T5 SHAPES EXTRUDED	52132
	AL 6063-T5 TUBE EXTRUDED	52133
	AL 6063-T52 SHAPES EXTRUDED	52139
	AL 6063-T6 WIRE EXTRUDED	52140
	AL 6063-T6 ROD EXTRUDED	52141
	AL 6063-T6 SHAPES EXTRUDED	52143
	AL 6063-T52 TUBE EXTRUDED	52144
	AL 6063-T6 TUBE EXTRUDED	52145
	AL 6063-T1 WIRE EXTRUDED	52153
	AL 6063-T1 ROD EXTRUDED	52154
	AL 6063-T1 BAR EXTRUDED	52155
	AL 6063-T1 SHAPES EXTRUDED	52156
	AL 6063-T1 TUBE EXTRUDED	52157
	AL 6063-T4 WIRE EXTRUDED	52158
	AL 6063-T4 ROD EXTRUDED	52159
	AL 6063-T4 BAR EXTRUDED	52160
	AL 6063-T4 SHAPES EXTRUDED	52161
	AL 6063-T4 TUBE EXTRUDED	52162
	AL 6063-T42 SHAPES EXTRUDED	52165
	AL 6063-T42 TUBE EXTRUDED	52166
	AL 7178-O WIRE EXTRUDED	52183
	AL 7178-O ROD EXTRUDED	52184
	AL 7178-O BAR EXTRUDED	52185
	AL 7178-O SHAPES EXTRUDED	52186
	AL 7178-O TUBE EXTRUDED	52187
	AL 7178-T6 WIRE EXTRUDED	52188
	AL 7178-T6 ROD EXTRUDED	52189
	AL 7178-T6 BAR EXTRUDED	52190

MSFC-HDBK-527 REV F 9999942 0005051 7

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
ASTM B221	AL 7178-T6 SHAPES EXTRUDED	52191
	AL 7178-T6 TUBE EXTRUDED	52192
	AL 7178-T6510 WIRE EXTRUDED	52193
	AL 7178-T6510 ROD EXTRUDED	52194
	AL 7178-T6510 BAR EXTRUDED	52195
	AL 7178-T6510 SHAPES EXTRUDED	52196
	AL 7178-T6510 TUBE EXTRUDED	52197
	AL 7178-T6511 WIRE EXTRUDED	52198
	AL 7178-T6511 ROD EXTRUDED	52199
	AL 7178-T6511 BAR EXTRUDED	52200
	AL 7178-T6511 SHAPES EXTRUDED	52201
	AL 7178-T6511 TUBE EXTRUDED	52202
	AL 7178-T62 WIRE EXTRUDED	52203
	AL 7178-T62 ROD EXTRUDED	52204
	AL 7178-T62 BAR EXTRUDED	52205
	AL 7178-T62 SHAPES EXTRUDED	52206
	AL 7178-T62 TUBE EXTRUDED	52207
	AL 7178-T76 WIRE EXTRUDED	52208
	AL 7178-T76 ROD EXTRUDED	52209
	AL 7178-T76 BAR EXTRUDED	52210
	AL 7178-T76 SHAPES EXTRUDED	52211
	AL 7178-T76 TUBE EXTRUDED	52212
	AL 7178-T76510 WIRE EXTRUDED	52213
	AL 7178-T76510 ROD EXTRUDED	52214
	AL 7178-T76510 BAR EXTRUDED	52215
	AL 7178-T76510 SHAPES EXTRUDED	52216
	AL 7178-T76510 TUBE EXTRUDED	52217
	AL 7178-T76511 WIRE EXTRUDED	52218
	AL 7178-T76511 ROD EXTRUDED	52219
	AL 7178-T76511 BAR EXTRUDED	52220
	AL 7178-T76511 SHAPES EXTRUDED	52221
	AL 7178-T76511 TUBE EXTRUDED	52222
	AL 6262-T6 WIRE EXTRUDED	52238
	AL 6262-T6 ROD EXTRUDED	52239
	AL 6262-T6 BAR EXTRUDED	52240
	AL 6262-T6 SHAPES EXTRUDED	52241
	AL 6262-T6 TUBE EXTRUDED	52242
	AL 6262-T6510 WIRE EXTRUDED	52243
	AL 6262-T6510 ROD EXTRUDED	52244
	AL 6262-T6510 BAR EXTRUDED	52245
	AL 6262-T6510 SHAPES EXTRUDED	52249
	AL 6262-T6510 TUBE EXTRUDED	52250
	AL 6262-T6511 WIRE EXTRUDED	52251
	AL 6262-T6511 ROD EXTRUDED	52252
	AL 6262-T6511 BAR EXTRUDED	52253
	AL 6262-T6511 SHAPES EXTRUDED	52254
	AL 6262-T6511 TUBE EXTRUDED	52255
	AL 5456-O BAR EXTRUDED	52274
	AL 5456-O ROD EXTRUDED	52275
	AL 5456-O SHAPES EXTRUDED	52276
	AL 5456-H111 SHAPES EXTRUDED	52277
	AL 5456-H112 SHAPES EXTRUDED	52278
	AL 5456-O TUBE EXTRUDED	52279
	AL 5456-H111 TUBE EXTRUDED	52280
	AL 5456-H112 TUBE EXTRUDED	52281

SPECIFICATION	DESIGNATION	MATCD
ASTM B221	AL 5456-O WIRE EXTRUDED	52282
	AL 2014-O BAR EXTRUDED	52355
	AL 2014-T4 BAR EXTRUDED	52356
	AL 2014-T4510 BAR EXTRUDED	52357
	AL 2014-T4511 BAR EXTRUDED	52358
	AL 2014-T42 BAR EXTRUDED	52359
	AL 2014-T6 BAR EXTRUDED	52360
	AL 2014-T6510 BAR EXTRUDED	52361
	AL 2014-T6511 BAR EXTRUDED	52362
	AL 2014-T62 BAR EXTRUDED	52363
	AL 2014-O ROD EXTRUDED	52364
	AL 2014-T4 ROD EXTRUDED	52365
	AL 2014-T4510 ROD EXTRUDED	52366
	AL 2014-T4511 ROD EXTRUDED	52367
	AL 2014-T42 ROD EXTRUDED	52368
	AL 2014-T6 ROD EXTRUDED	52369
	AL 2014-T6510 ROD EXTRUDED	52370
	AL 2014-T6511 ROD EXTRUDED	52371
	AL 2014-T62 ROD EXTRUDED	52372
	AL 2014-O SHAPES EXTRUDED	52373
	AL 2014-T4 SHAPES EXTRUDED	52374
	AL 2014-T4510 SHAPES EXTRUDED	52375
	AL 2014-T4511 SHAPES EXTRUDED	52376
	AL 2014-T42 SHAPES EXTRUDED	52377
	AL 2014-T6 SHAPES EXTRUDED	52378
	AL 2014-T6510 SHAPES EXTRUDED	52379
	AL 2014-T6511 SHAPES EXTRUDED	52380
	AL 2014-T62 SHAPES EXTRUDED	52381
	AL 2014-O TUBE EXTRUDED	52382
	AL 2014-T4 TUBE EXTRUDED	52383
	AL 2014-T4510 TUBE EXTRUDED	52384
	AL 2014-T4511 TUBE EXTRUDED	52385
	AL 2014-T42 TUBE EXTRUDED	52386
	AL 2014-T6 TUBE EXTRUDED	52387
	AL 2014-T6510 TUBE EXTRUDED	52388
	AL 2014-T6511 TUBE EXTRUDED	52389
	AL 2014-T62 TUBE EXTRUDED	52390
	AL 2014-O WIRE EXTRUDED	52391
	AL 2014-T4 WIRE EXTRUDED	52392
	AL 2014-T4510 WIRE EXTRUDED	52393
	AL 2014-T4511 WIRE EXTRUDED	52394
	AL 2014-T42 WIRE EXTRUDED	52395
	AL 2014-T6 WIRE EXTRUDED	52396
	AL 2014-T6510 WIRE EXTRUDED	52397
	AL 2014-T6511 WIRE EXTRUDED	52398
	AL 2014-T62 WIRE EXTRUDED	52399
	AL 2219-T62 WIRE EXTRUDED	52602
	AL 2219-T62 ROD EXTRUDED	52603
	AL 2219-T62 SHAPES EXTRUDED	52604
	AL 2219-T62 TUBE EXTRUDED	52610
	AL 2219-T81 TUBE EXTRUDED	52611
	AL 7075-T73511 TUBE EXTRUDED	52917
	AL 7075-O WIRE EXTRUDED	52918
	AL 7075-O ROD EXTRUDED	52919
	AL 3003-O SHAPES EXTRUDED	52985

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005052 9

SPECIFICATION	DESIGNATION	MATCD
ASTM B221	AL 3003-H112 WIRE EXTRUDED	52986
	AL 3003-H112 ROD EXTRUDED	52987
	AL 3003-H112 BAR EXTRUDED	52988
	AL 3003-H112 SHAPES EXTRUDED	52989
	AL 3003-H112 TUBE EXTRUDED	52990
	AL 2024-T3510 WIRE EXTRUDED	53041
	AL 2024-T3511 WIRE EXTRUDED	53044
	AL 2024-T81 BAR EXTRUDED	53058
	AL 2024-T81 ROD EXTRUDED	53059
	AL 2024-T81 SHAPES EXTRUDED	53060
	AL 2024-T8510 SHAPES EXTRUDED	53065
	AL 2024-T8511 WIRE EXTRUDED	53066
	AL 2024-T8511 BAR EXTRUDED	53067
ASTM B230	AL 1350-H19 WIRE	51590
ASTM B234	AL 6061-T4 TUBE	10732
	AL 6061-T6 TUBE CONDENSER	51265
	AL 3003-H14 TUBE CONDENSER CLAD	51624
	AL 3003-H25 TUBE CONDENSER CLAD	51625
	AL 5052-H32 TUBE CONDENSER	51942
	AL 5052-H34 TUBE CONDENSER	51943
	AL 5454-H32 TUBE CONDENSER	52865
	AL 5454-H34 TUBE CONDENSER	52866
	AL 3003-H14 TUBE CONDENSER	53008
	AL 3003-H25 TUBE CONDENSER	53009
ASTM B241	AL 2219-T62 TUBE	10412
	AL 6061-T4 TUBE	10732
	AL 2219-T81 TUBE	50517
	AL 2219-T8511 TUBE EXTRUDED SEAMLESS	51080
	AL 2024-O TUBE EXTRUDED	51117
	AL 2024-T3 TUBE EXTRUDED	51118
	AL 2024-T3510 TUBE EXTRUDED	51120
	AL 2024-T3511 TUBE EXTRUDED	51121
	AL 2024-T42 TUBE EXTRUDED	51122
	AL 2024-T81 TUBE EXTRUDED	51123
	AL 6061-O PIPE	51270
	AL 6061-T4 PIPE	51271
	AL 6061-T4510 PIPE	51272
	AL 6061-T4511 PIPE	51273
	AL 6061-T42 PIPE	51274
	AL 6061-T62 PIPE	51275
	AL 6061-T6510 PIPE	51277
	AL 6061-T6511 PIPE	51278
	AL 6061-T4510 TUBE EXTRUDED	51343
	AL 6061-T42 TUBE EXTRUDED	51345
	AL 6061-T51 TUBE EXTRUDED	51346
	AL 6061-T62 TUBE EXTRUDED	51350
	AL 6061-T6 PIPE	51369
	AL 7075-T73510 TUBE EXTRUDED	51439
	AL 7075-O TUBE EXTRUDED	51458
	AL 7075-T6 TUBE EXTRUDED	51463
	AL 7075-T62 TUBE EXTRUDED	51466
	AL 7075-T6510 TUBE EXTRUDED	51471
	AL 7075-T6511 TUBE EXTRUDED	51476
	AL 5652-O TUBE EXTRUDED SEAMLESS	51725
	AL 5652-H112 TUBE EXTRUDED SEAMLESS	51726
ASTM B241	AL 5254-O TUBE EXTRUDED SEAMLESS	51736
	AL 5254-H112 TUBE EXTRUDED SEAMLESS	51737
	AL 1100-O TUBE EXTRUDED	51983
	AL 1100-H112 TUBE EXTRUDED	51984
	AL 1060-O TUBE EXTRUDED	52076
	AL 1060-H112 TUBE EXTRUDED	52077
	AL 6063-T6 PIPE	52135
	AL 6063-T1 SHAPES EXTRUDED	52156
	AL 6063-T62 TUBE EXTRUDED SEAMLESS	52163
	AL 5456-O TUBE EXTRUDED SEAMLESS	52283
	AL 5456-H111 TUBE EXTRUDED SEAMLESS	52284
	AL 5456-H112 TUBE EXTRUDED SEAMLESS	52285
	AL 2014-O TUBE EXTRUDED	52382
	AL 2014-T4 TUBE EXTRUDED	52383
	AL 2014-T4510 TUBE EXTRUDED	52384
	AL 2014-T4511 TUBE EXTRUDED	52385
	AL 2014-T42 TUBE EXTRUDED	52386
	AL 2014-T6 TUBE EXTRUDED	52387
	AL 2014-T6510 TUBE EXTRUDED	52388
	AL 2014-T6511 TUBE EXTRUDED	52389
	AL 2014-T62 TUBE EXTRUDED	52390
	AL 2014-O TUBE EXTRUDED SEAMLESS	52400
	AL 2014-T4 TUBE EXTRUDED SEAMLESS	52401
	AL 2014-T4510 TUBE EXTRUDED SEAMLESS	52402
	AL 2014-T4511 TUBE EXTRUDED SEAMLESS	52403
	AL 2014-T42 TUBE EXTRUDED SEAMLESS	52404
	AL 2014-T6 TUBE EXTRUDED SEAMLESS	52405
	AL 2014-T6510 TUBE EXTRUDED SEAMLESS	52406
	AL 2014-T6511 TUBE EXTRUDED SEAMLESS	52407
	AL 2014-T62 TUBE EXTRUDED SEAMLESS	52408
	AL 1060-O TUBE EXTRUDED SEAMLESS	52563
	AL 1100-O TUBE EXTRUDED SEAMLESS	52586
	AL 1100-H112 TUBE EXTRUDED SEAMLESS	52587
	AL 2219-O TUBE EXTRUDED SEAMLESS	52605
	AL 2219-T31 TUBE EXTRUDED SEAMLESS	52606
	AL 2219-T3510 TUBE EXTRUDED SEAMLESS	52607
	AL 2219-T3511 TUBE EXTRUDED SEAMLESS	52608
	AL 2219-T8510 TUBE EXTRUDED SEAMLESS	52609
	AL 2219-T62 TUBE EXTRUDED SEAMLESS	52612
	AL 2219-T81 TUBE EXTRUDED SEAMLESS	52613
	AL 5052-O TUBE EXTRUDED SEAMLESS	52802
	AL 5086-O TUBE EXTRUDED SEAMLESS	52833
	AL 5086-H111 TUBE EXTRUDED SEAMLESS	52834
	AL 5086-H112 TUBE EXTRUDED SEAMLESS	52835
	AL 5454-O TUBE EXTRUDED SEAMLESS	52862
	AL 5454-H111 TUBE EXTRUDED SEAMLESS	52863
	AL 5454-H112 TUBE EXTRUDED SEAMLESS	52864
	AL 3003-O TUBE EXTRUDED SEAMLESS CLAD	52872
	AL 3003-H112 TUBE EXTRUDED SEAMLESS CLAD	52873
	AL 6063-O TUBE EXTRUDED SEAMLESS	52885
	AL 6063-T1 TUBE EXTRUDED SEAMLESS	52886
	AL 6063-T4 TUBE EXTRUDED SEAMLESS	52893
	AL 6063-T42 TUBE EXTRUDED SEAMLESS	52894
	AL 6063-T5 TUBE EXTRUDED SEAMLESS	52895
	AL 6063-T6 TUBE EXTRUDED SEAMLESS	52896

MSFC-HDBK-527 REV F 9999942 0005053 0

Information Handling Services, 2000

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
ASTM B241	AL 7075-T73511 TUBE EXTRUDED	52917
	AL 7075-O TUBE EXTRUDED SEAMLESS	52920
	AL 7075-T6 TUBE EXTRUDED SEAMLESS	52921
	AL 7075-T62 TUBE EXTRUDED SEAMLESS	52922
	AL 7075-T6510 TUBE EXTRUDED SEAMLESS	52923
	AL 7075-T6511 TUBE EXTRUDED SEAMLESS	52924
	AL 7075-T73 TUBE EXTRUDED SEAMLESS	52925
	AL 7075-T73510 TUBE EXTRUDED SEAMLESS	52926
	AL 7075-T73511 TUBE EXTRUDED SEAMLESS	52927
	AL 7178-O TUBE EXTRUDED SEAMLESS	52956
	AL 7178-T6 TUBE EXTRUDED SEAMLESS	52957
	AL 7178-T6510 TUBE EXTRUDED SEAMLESS	52958
	AL 7178-T62 TUBE EXTRUDED SEAMLESS	52960
	AL 3003-O TUBE EXTRUDED SEAMLESS	52991
	AL 3003-H112 TUBE EXTRUDED SEAMLESS	52992
	AL 3003-H112 PIPE	52993
	AL 3003-H18 PIPE	52994
	AL 2024-O TUBE EXTRUDED SEAMLESS	53031
	AL 2024-T3 TUBE EXTRUDED SEAMLESS	53034
	AL 2024-T3510 TUBE EXTRUDED SEAMELSS	53040
	AL 2024-T3511 TUBE EXTRUDED SEAMLESS	53042
	AL 2024-T42 TUBE EXTRUDED SEAMLESS	53049
	AL 2024-T81 TUBE EXTRUDED SEAMLESS	53062
	AL 2024-T8510 TUBE EXTRUDED SEAMLESS	53068
	AL 2024-T8511 TUBE EXTRUDED SEAMLESS	53069
ASTM B247	AL 2219-T852 FORGING HAND	10007
	AL 2219-T6 FORGING HAND	10014
	AL 7075-T7352 FORGING	10048
	AL 2219-T852 FORGING	30106
	AL 7075-T6 FORGING	50101
	AL 2219-T6 FORGING DIE	50590
	AL 6061-T6 FORGING DIE	51359
	AL 6061-T6 FORGING HAND	51361
	AL 7075-T73 FORGING DIE	51485
	AL 7075-T652 FORGING HAND	51486
	AL 7075-T73 FORGING HAND	51487
	AL 7049-T73 FORGING HAND	51786
	AL 7049-T7352 FORGING HAND	51787
	AL 7049-T73 FORGING DIE	51788
	AL 4032-T6 FORGING DIE	51826
	AL 1100-H112 FORGING DIE	52003
	AL 7050-T7452 FORGING HAND	52298
	AL 7050-T74 FORGING DIE	52299
	AL 2014-T6 FORGING DIE	52414
	AL 2014-T4 FORGING DIE	52415
	AL 2014-T6 FORGING HAND	52416
	AL 2014-T652 FORGING HAND	52417
	AL 7075-T6 FORGING DIE	52928
	AL 7075-T7352 FORGING DIE	52929
	AL 7075-T6 FORGING HAND	52930
	AL 7075-T7352 FORGING HAND	52931
	AL 3003-H112 FORGING DIE	53021
	AL 2219-T6 FORGING	53072
ASTM B280	COPPER TUBE ANNEALED NI PLATED SPLICE	10353
ASTM B3	COPPER ALLOY 102 WIRE	10354

SPECIFICATION	DESIGNATION	MATCD
ASTM B308	AL 6061-T6 SHAPES EXTRUDED STRUCTURAL	51371
ASTM B313	AL 6061-T4 TUBE	10732
	AL 5086-O TUBE WELDED	51024
	AL 5086-H32 TUBE WELDED	51025
	AL 5086-H34 TUBE WELDED	51026
	AL 5086-H36 TUBE WELDED	51027
	AL 6061-O TUBE	51266
	AL 6061-T6 TUBE WELDED	51268
	AL 3004-O TUBE WELDED	51604
	AL 3004-H32 TUBE WELDED	51605
	AL 3004-H34 TUBE WELDED	51606
	AL 3004-H36 TUBE WELDED	51607
	AL 3004-H38 TUBE WELDED	51608
	AL 3003-H14 TUBE WELDED	51628
	AL 3004-O TUBE WELDED CLAD	51761
	AL 3004-H32 TUBE WELDED CLAD	51762
	AL 3004-H34 TUBE WELDED CLAD	51763
	AL 3004-H36 TUBE WELDED CLAD	51764
	AL 3004-H38 TUBE WELDED CLAD	51765
	AL 5050-O TUBE WELDED	51806
	AL 5050-H32 TUBE WELDED	51807
	AL 5050-H34 TUBE WELDED	51808
	AL 5050-H36 TUBE WELDED	51809
	AL 5050-H38 TUBE WELDED	51810
	AL 5052-O TUBE WELDED	51944
	AL 5052-H36 TUBE WELDED	51945
	AL 5052-H38 TUBE WELDED	51946
	AL 1100-O TUBE WELDED	51991
	AL 1100-H12 TUBE WELDED	51992
	AL 1100-H14 TUBE WELDED	51993
	AL 1100-H16 TUBE WELDED	51994
	AL 1100-H18 TUBE WELDED	51996
	AL 5154-O TUBE WELDED	52051
	AL 5154-H32 TUBE WELDED	52052
	AL 5154-H34 TUBE WELDED	52053
	AL 5154-H36 TUBE WELDED	52054
	AL 5154-H38 TUBE WELDED	52055
	AL 5052-H32 TUBE WELDED	52803
	AL 5052-H34 TUBE WELDED	52804
	AL 3003-O TUBE WELDED	53010
	AL 3003-H12 TUBE WELDED	53011
	AL 3003-H16 TUBE WELDED	53012
	AL 3003-H18 TUBE WELDED	53013
ASTM B314	AL 1350-H14 WIRE	51591
ASTM B316	AL 2117-H13 ROD	10224
	AL 2117-T4 WIRE RIVET AND COLD HEADING	50583
	AL 6061-H13 ROD RIVET AND COLD HEADING	50635
	AL 6061-H13 WIRE RIVET AND COLD HEADING	50636
	AL 2219-H13 WIRE RIVET AND COLD HEADING	51082
	AL 2219-T6 WIRE RIVET AND COLD HEADING	51083
	AL 2219-H13 ROD RIVET AND COLD HEADING	51084
	AL 2219-T6 ROD RIVET AND COLD HEADING	51085
	AL 2024-O WIRE RIVET AND COLD HEADING	51129
	AL 2024-H13 WIRE RIVET AND COLD HEADING	51130
	AL 2024-T4 WIRE RIVET AND COLD HEADING	51131

MSFC-HDBK-527 REV F ■ 9999942 0005054 2 ■

SPECIFICATION	DESIGNATION	MATCD
ASTM B316	AL 2024-O ROD RIVET AND COLD HEADING	51133
	AL 2024-H13 ROD RIVET AND COLD HEADING	51134
	AL 2024-T4 ROD RIVET AND COLD HEADING	51135
	AL 5056-H32 WIRE RIVET AND COLD HEADING	51210
	AL 5056-H32 ROD RIVET AND COLD HEADING	51211
	AL 6061-T6 WIRE RIVET AND COLD HEADING	51279
	AL 6061-T6 ROD RIVET AND COLD HEADING	51280
	AL 7075-H13 WIRE RIVET AND COLD HEADING	51497
	AL 7075-H13 ROD RIVET AND COLD HEADING	51498
	AL 7075-T73 WIRE RIVET AND COLD HEADING	51499
	AL 7075-T73 ROD RIVET AND COLD HEADING	51500
	AL 5005-O WIRE RIVET AND COLD HEADING	51662
	AL 5005-O ROD RIVET AND COLD HEADING	51663
	AL 5005-H32 WIRE RIVET AND COLD HEADING	51664
	AL 5005-H32 ROD RIVET AND COLD HEADING	51665
	AL 6053-T61 WIRE RIVET AND COLD HEADING	51691
	AL 6053-T61 ROD RIVET AND COLD HEADING	51692
	AL 6053-O WIRE RIVET AND COLD HEADING	51693
	AL 6053-O ROD RIVET AND COLD HEADING	51694
	AL 6053-H13 WIRE RIVET AND COLD HEADING	51695
	AL 6053-H13 ROD RIVET AND COLD HEADING	51696
	AL 2117-O WIRE RIVET AND COLD HEADING	51766
	AL 2117-O ROD RIVET AND COLD HEADING	51767
	AL 2117-H15 WIRE RIVET AND COLD HEADING	51768
	AL 2117-H15 ROD RIVET AND COLD HEADING	51769
	AL 5052-O WIRE RIVET AND COLD HEADING	51948
	AL 5052-H32 WIRE RIVET AND COLD HEADING	51949
	AL 5052-O ROD RIVET AND COLD HEADING	51950
	AL 5052-H32 ROD RIVET AND COLD HEADING	51951
	AL 1100-O WIRE RIVET AND COLD HEADING	51997
	AL 1100-H14 WIRE RIVET AND COLD HEADING	51998
	AL 1100-O ROD RIVET AND COLD HEADING	51999
	AL 1100-H14 ROD RIVET AND COLD HEADING	52000
	AL 7178-O WIRE RIVET AND COLD HEADING	52223
	AL 7178-H13 WIRE RIVET AND COLD HEADING	52224
	AL 7178-T6 WIRE RIVET AND COLD HEADING	52225
	AL 7178-O ROD RIVET AND COLD HEADING	52226
	AL 7178-H13 ROD RIVET AND COLD HEADING	52227
	AL 7178-T6 ROD RIVET AND COLD HEADING	52228
	AL 7050-O WIRE RIVET AND COLD HEADING	52300
	AL 7050-H13 WIRE RIVET AND COLD HEADING	52301
	AL 7050-O ROD RIVET AND COLD HEADING	52302
	AL 7050-H13 ROD RIVET AND COLD HEADING	52303
	AL 7050-T7 WIRE RIVET AND COLD HEADING	52304
	AL 7050-T7 ROD RIVET AND COLD HEADING	52305
	AL 7075-O RIVET AND WIRE COLD HEADING	52909
	AL 7075-O RIVET AND ROD COLD HEADING	52910
	AL 3003-O RIVET AND WIRE COLD HEADING	53017
	AL 3003-O RIVET AND ROD COLD HEADING	53018
	AL 3003-H14 RIVET AND WIRE COLD HEADING	53019
	AL 3003-H14 RIVET AND ROD COLD HEADING	53020
	AL 2117-H13 RIVET AND ROD COLD HEADING	53070
	AL 2117-T4 RIVET AND ROD COLD HEADING	53071
ASTM B317	AL 6101 FORMS EXTRUDED METAL	10736
	AL 6101-T6 CONDUCTOR	51773
ASTM B317	AL 6101-T61 CONDUCTOR	51774
	AL 6101-T63 CONDUCTOR	51775
	AL 6101-T64 CONDUCTOR	51776
	AL 6101-T65 CONDUCTOR	51777
	AL 6101-H111 CONDUCTOR	51778
ASTM B323	AL 1350-H14 WIRE	51591
ASTM B338	TITANIUM COMM PURE TUBE ANNEALED <55KSI	10298
ASTM B345	AL 6061-T4 TUBE	10732
	AL 5086-O PIPE	51028
	AL 5086-H111 PIPE	51029
	AL 5086-H112 PIPE	51031
	AL 6061-O PIPE	51270
	AL 6061-T4 PIPE	51271
	AL 6061-T4510 PIPE	51272
	AL 6061-T4511 PIPE	51273
	AL 6061-T42 PIPE	51274
	AL 6061-T62 PIPE	51275
	AL 6061-T6510 PIPE	51277
	AL 6061-T6511 PIPE	51278
	AL 6061-T6 PIPE	51369
	AL 6070-T6 PIPE	51676
	AL 6070-T62 PIPE	51677
	AL 6351-T5 PIPE	51784
	AL 6351-T6 PIPE	51785
	AL 6063-O PIPE	52136
	AL 6063-T1 PIPE	52167
	AL 6063-T4 PIPE	52168
	AL 6063-T42 PIPE	52169
	AL 6063-T5 PIPE	52170
	AL 6063-T52 PIPE	52171
	AL 6063-T6 PIPE	52172
	AL 6063-T62 PIPE	52173
	AL 1060-O PIPE	52569
	AL 1060-H112 PIPE	52570
ASTM B348 GR3	TITANIUM COMM PURE BAR ANNEALED 55KSI	10055
ASTM B355	WIRE CU,NI COATED ELECTRICAL	10223
ASTM B373	AL 1145-O FOIL	51699
	AL 1145-H19 FOIL	51700
ASTM B396	AL 5005-H19 WIRE	51661
ASTM B398	AL 6201-T81 WIRE	51689
ASTM B399	AL 6201-T81 CONDUCTOR	51690
ASTM B404	AL 1060-O TUBE CONDENSER	52092
ASTM B407	INCOLOY 800 PIPE ANNEALED	53343
	INCOLOY 800 PIPE COLD DRAWN & ANNEALED	53344
	INCOLOY 800 PIPE 1/2 HARD	53345
	INCOLOY 800 PIPE FULL HARD	53346
	INCOLOY 800 TUBE SEAMLESS ANNEALED	53347
	INCOLOY 800 TUBE SEAMLESS COLD DRAWN & A	53348
	INCOLOY 800 TUBE SEAMLESS 1/2 HARD	53349
	INCOLOY 800 TUBE SEAMLESS FULL HARD	53350
ASTM B408	INCOLOY 800 ROD HOT FINISHED	53351
	INCOLOY 800 ROD COLD DRAWN & ANNEALED	53352
	INCOLOY 800 BAR HOT FINISHED	53353
	INCOLOY 800 BAR COLD DRAWN & ANNEALED	53354
ASTM B409	INCOLOY 800 PLATE ANNEALED	53355

MSFC-HDBK-527 REV F 9999942 0005055 4

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
ASTM B409	INCOLOY 800 PLATE AS ROLLED	53356
	INCOLOY 800 PLATE ANNEALED	53357
	INCOLOY 800 SHEET AS ROLLED	53358
	INCOLOY 800 SHEET COLD DRAWN & ANNEALED	53359
	INCOLOY 800 STRIP COLD DRAWN & ANNEALED	53360
ASTM B429	AL 6061-T6 PIPE	51369
	AL 6063-T6 PIPE EXTRUDED STRUCTURAL	52138
	AL 6063-T6 TUBE STRUCTURAL EXTRUDED	52890
ASTM B444	INCONEL 625 TUBE ANNEALED	10403
ASTM B453	COPPER 62CU CDA350 BRASS COPPER	10372
ASTM B483	AL 1100-O TUBE	10340
	AL 6061-T4 TUBE	10732
	AL 6061-O TUBE DRAWN	51261
	AL 6061-T42 TUBE DRAWN	51262
	AL 6061-T6 TUBE DRAWN	51263
	AL 6061-T62 TUBE DRAWN	51264
	AL 5005-O TUBE DRAWN	51666
	AL 5050-O TUBE DRAWN	51801
	AL 5050-H32 TUBE DRAWN	51802
	AL 5050-H34 TUBE DRAWN	51803
	AL 5050-H36 TUBE DRAWN	51804
	AL 5050-H38 TUBE DRAWN	51805
	AL 5052-O TUBE DRAWN	51936
	AL 5052-H32 TUBE DRAWN	51937
	AL 5052-H34 TUBE DRAWN	51938
	AL 5052-H36 TUBE DRAWN	51939
	AL 5052-H38 TUBE DRAWN	51940
	AL 1100-H12 TUBE DRAWN	51985
	AL 1100-H14 TUBE DRAWN	51986
	AL 1100-H16 TUBE DRAWN	51987
	AL 1100-H18 TUBE DRAWN	51988
	AL 1100-H113 TUBE DRAWN	51989
	AL 1060-O TUBE DRAWN	52086
	AL 1060-H12 TUBE DRAWN	52087
	AL 1060-H14 TUBE DRAWN	52088
	AL 1060-H18 TUBE DRAWN	52089
	AL 1060-H113 TUBE DRAWN	52090
	AL 6063-O TUBE DRAWN	52134
	AL 6063-T4 TUBE DRAWN	52146
	AL 6063-T6 TUBE DRAWN	52147
	AL 6063-T83 TUBE DRAWN	52148
	AL 6063-T831 TUBE DRAWN	52149
	AL 6063-T832 TUBE DRAWN	52150
	AL 6063-T42 TUBE DRAWN	52151
	AL 6063-T62 TUBE DRAWN	52152
	AL 6262-T6 TUBE DRAWN	52246
	AL 6262-T62 TUBE DRAWN	52247
	AL 6262-T9 TUBE DRAWN	52248
	AL 1100-O TUBE DRAWN	52697
	AL 3003-O TUBE DRAWN	52996
	AL 3003-H12 TUBE DRAWN	52997
	AL 3003-H14 TUBE DRAWN	52998
	AL 3003-H16 TUBE DRAWN	52999
	AL 3003-H18 TUBE DRAWN	53000
	AL 3003-H113 TUBE DRAWN	53001

SPECIFICATION	DESIGNATION	MATCD
ASTM B491	AL 1235-H111 TUBE EXTRUDED ROUND	51827
	AL 1235-H112 TUBE EXTRUDED ROUND	51828
	AL 1100-H112 TUBE EXTRUDED	51984
	AL 1100-H112 TUBE COILED EXTRUDED	52588
	AL 6063-T1 TUBE ROUND EXTRUDED	52887
	AL 3003-H112 TUBE ROUND EXTRUDED	52995
ASTM B501	WIRE CU AG COATED CLAD	10733
ASTM B531	AL 5005-O ROD ROLLED	51660
ASTM B534	BE-CU #175 WIRE CONDITION A	10149
	BE-CU #175 SHEET	50959
	BE-CU #175 PLATE	50960
ASTM B547	AL 6061-T4 TUBE	10732
	AL 5086-O TUBE WELDED	51024
	AL 5086-H32 TUBE WELDED	51025
	AL 5086-H34 TUBE WELDED	51026
	AL 5086-H36 TUBE WELDED	51027
	AL 6061-T451 TUBE	51267
	AL 6061-T6 TUBE WELDED	51268
	AL 6061-T651 TUBE WELDED	51269
	AL 3004-O TUBE WELDED	51604
	AL 3004-H32 TUBE WELDED	51605
	AL 3004-H34 TUBE WELDED	51606
	AL 3004-H36 TUBE WELDED	51607
	AL 3003-O TUBE WELDED CLAD	51626
	AL 3003-H12 TUBE WELDED CLAD	51627
	AL 3003-H14 TUBE WELDED	51628
	AL 3003-H112 TUBE WELDED CLAD	51629
	AL 5050-O TUBE WELDED	51806
	AL 5050-H32 TUBE WELDED	51807
	AL 5050-H34 TUBE WELDED	51808
	AL 5050-H36 TUBE WELDED	51809
	AL 5454-O TUBE WELDED	51907
	AL 5454-H32 TUBE WELDED	51908
	AL 5454-H34 TUBE WELDED	51909
	AL 5454-H112 TUBE WELDED	51910
	AL 5052-H112 TUBE ROUND	51947
	AL 1100-O TUBE WELDED	51991
	AL 1100-H12 TUBE WELDED	51992
	AL 1100-H14 TUBE WELDED	51993
	AL 1100-H16 TUBE WELDED	51994
	AL 5154-O TUBE WELDED	52051
	AL 5154-H32 TUBE WELDED	52052
	AL 5154-H34 TUBE WELDED	52053
	AL 5154-H36 TUBE WELDED	52054
	AL 5052-O TUBE ROUND	52805
	AL 5052-H32 TUBE ROUND	52806
	AL 5052-H34 TUBE ROUND	52807
	AL 5052-H36 TUBE ROUND	52808
	AL 3004-O TUBE ROUND CLAD	52874
	AL 3004-H32 TUBE ROUND CLAD	52875
	AL 3004-H34 TUBE ROUND CLAD	52876
	AL 3004-H36 TUBE ROUND CLAD	52877
	AL 3003-O TUBE WELDED	53010
	AL 3003-H12 TUBE WELDED	53011
	AL 3003-H16 TUBE WELDED	53012

MSFC-HDBK-527 REV F 9999942 0005056 6

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
ASTM B547	AL 3003-H112 TUBE WELDED	53014
	AL 3003 TUBE WELDED CLAD	53073
ASTM B5SS	PALINEY #7 COMP D	10608
ASTM B609	AL 1350 CONDUCTOR SOLID ROUND	51592
ASTM B75	COPPER TUBE SEAMLESS	10483
ASTM B98	COPPER 661/SIL ALLOY ROD	50504
ASTM E 230	T/C ALLOY PLATINUM/PT-RH	10665
ASTM-A-269	CRES 304 TUBE/PTFE ANNEALED	10413
ASTM-A-312	CRES 304 TUBE/PTFE ANNEALED	10413
ASTM-A276	CRES 302 BAR COLD DRAWN 100KSI	10089
ASTM-A351	CRES 316 CASTING INVESTMENT ANNEALED	10159
ASTM-B-122 #2	65CU-18NI-17ZNALLOY NO 752	10612
ASTM-B-122 #5	COPPER 30NI ALLOY NO 715	10607
ASTM-B-3-1	BRONZE,TELNIC (99.9% CU)	10602
ASTM-B211	AL 2011-T451 ROD COLD FINISHED	52542
ASTM-B584	BRONZE PHOSPHOR SAE 660	10360
AWS A5.14-76	WELD WIRE NI-CU BASE	50137
AWS A5.5	WELD WIRE STEEL E10018	10730
BAG-18	BRAZE 60AG 30CU 10SN	10242
BAG-19	BRAZE 92.5 AG 7.2 CU .22 LI	10339
BAU-4	BRAZE 82AU 18NI	10119
BERIUM METAL	BRONZE PHOSPHOR-ALL FORMS	10322
BNI-1	BRAZE 73NI 4.5SI 14CR 3.1B4.5	10245
BNI-2	BRAZE 82NI 4.5SI 7CR 3FE 3.1B	10479
BNI-3	BRAZE 92NI 4.5SI 3.1B	10246
CM24.14-01	RENE 95 BAR	30085
	RENE 95 SHAPE	50897
	RENE 95 FORGING	50898
COMMERCIAL GR	CRES 440 SHEET	50097
	CRES 440 BAR	50819
	CRES 440 ROD	50820
COMMERICAL GR	CRES 440 PLATE	50818
CU96 BE.6 CO2.6	BE-CU #175	10638
DIN 1756	COPPER 63 ZN37 SHEET	50244
	COPPER 63 ZN37 ROD	50841
DIN 17660	COPPER 63 ZN37 SHEET	50244
	COPPER 63 ZN37 ROD	50841
ESPD 101A	AL KO-1 CASTINGS SAND	51167
ESPD 102A	AL KO-1 CASTINGS PREMIUM	51168
FED STD 66	CRES 300 SERIES	10268
	CRES 302 WIRE SPRING TEMPER B	10391
	CRES 303/305 BAR	10512
	CRES 303 BAR FREE MACHINE	30080
FED-STD-66	STEEL 4XXX <200 KSI	10513
	STEEL HIGH CARBON >200 KSI	10515
	STEEL 1008-1020 <180 KSI	10648
	STEEL 8735 SHEET >200 KSI	30087
	CRES 410 BAR ANNEALED	30114
	STEEL 4XXX >200 KSI	50110
	STEEL 1117 COLD FINISH <180KSI	50522
	STEEL 1113 COLD FINISH <180KSI	50523
FSCM05341SPRING	STEEL 6150 (RC 46-50)	30079
HM STD SVHS7204	CB 103 BAR ANNEALED	10660
HS 5873 CL2	BRAZE AL ALLOY 10SI 1.2MN	10721
KARMA	NICKEL 30CR 3AL 3FE	30145

SPECIFICATION	DESIGNATION	MATCD
LB0130-018	AL 5056 WIRE SCREEN	10377
LB0170-103I&II	MONEL 400 67NI 30CU WIRE ANNEALED	10222
LB0170-194	STEEL T-I 13V 11CR 3AL SPRING WIRE	10696
LB0170-107	NICKEL 99% ELECTROFORMED PARTS	10320
LTV-RFCA	MAGNET 17CO-83FE ALLOY	10689
MA0109-313	PLATING SILVER	10039
MA0109-308	COATING AL PLASMA	10472
MA0109-310	COATING ANODIZING, BERYLLIUM	30119
MA0109-311	PLATING NICKEL ELECTRODEPOSIT	10308
MAS 5643	STEEL TOOL 01 RC24-27	30098
MB0160-013	CRES 17PH-4MO H1150M CASTING	10077
MB0160-015	CRES 14PH-8MO H1050 SHEET	10081
MB0160-018	CRES 17PH-4MO H1150M BAR EXTRUDED	10037
MB0160-021	CRES 440C BAR QUENCHED AND TEMPERED	10106
MB0160-022	CRES 17PH-4MO H1150M FORGING EXTRUSION V	10075
MB0160-031	CRES 15PH-7MO SHEET	10264
	CRES 15PH-7MO PLATE	50730
MB0160-036	CRES 15PH-5MO H1150M BAR	10078
	CRES 15PH-5MO H1025 BAR	10389
MB0160-045	CRES 321 FOIL	10380
MB0160-046	CRES 304 BAR ANNEALED	10351
MB0170-055	BE 2% BEO SHEET	30044
MB0170-069	INCONEL 601 SHEET ANNEALED	10140
MB0170-070	INCONEL 625 STRIP ANNEALED	10141
MB0170-073	WELD WIRE TI 6AL 4V ELI BAR	10166
	WELD WIRE ELI TI 5AL 2.5SN	10168
	WELD WIRE ELI TI 6AL 4V	10169
	WELD WIRE NI BASE INCO 718	10189
	WELD WIRE NI BASE INCO 62	10190
	WELD WIRE CO BASE HAYNES 188	10194
MB0170-076	INCONEL 718 BAR ST1900F	10127
MB0170-078	AL 5083-H32 SHEET	10016
	AL 6061-T4 SHEET	10018
	AL 5052-H38 SHEET	50274
MB0170-082	TITANIUM 6AL 4V PLATE DIFFUSION BOND	10034
MB0170-083	AL 2419-T8XX SHEET	10273
MB0170-090	AL 7075-T76XXX EXTR EXFR RES	10041
MB0170-091	AL 7075-T7352 FORGING	10048
MB0170-092	AL 2219-T852 FORGING HAND	10007
MB0170-101	TITANIUM 3AL 2.5V FOIL ANNEALED	10310
MB0170-102	ELGILOY RC55 WIRE SPRING	10146
MB0170-103	HAYNES 188 SHEET ANNEALED	10397
MBO 170-066	HAYNES 188 FOIL ANNEALED	10142
MBO125-041	PLATING NIICKEL TIN ELECTROLESS	10274
MBO160-003	CRES 17PH-4MO H1025 EXTRUSIONS	10425
	CRES 17PH-4MO H1150 BAR EXTRUDED	10427
	CRES 17PH-4MO H1150 FORGING EXTRUDED	50737
MBO160-007	CRES 304L TUBE CONDITION A & B	10093
MBO160-015	CRES 14PH-8MO H1050 STRIP	50719
MBO160-016	CRES 304L WIRE SCREEN	10318
	CRES 316L WIRE SCREEN	50792
MBO160-036	DELETED SEE 50223	10003
	CRES 15PH-5MO H1150 BAR	10387
	CRES 15PH-5MO H1025 FORGING	50720
	CRES 15PH-5MO H1150 FORGING	50727

MSFC-HDBK-527 REV F ■ 9999942 0005057 8 ■

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
MB0160-037	CRES 304L BAR ANNEALED	10233
	CRES 304L FORGING ANNEALED VM	50788
	CRES 304L ROD ANNEALED VM	50789
MB0160-042	STEEL 9NI 4CO (.20C) BAR 190 KSI	10202
	STEEL 9NI 4CO (.20C) FORGING 190 KSI	50931
MB0160-044	CRES 21-6-9 SHEET ANNEALED	10103
	CRES 21-6-9 PLATE ANNEALED	50761
	CRES 21-6-9 STRIP ANNEALED	50762
MB0160-046	CRES 304 FORGING ANNEALED	50775
MB0160-047 TY 1	INCONEL X750 WIRE SPRING STA	10695
MB0160-048	VELCRO (304/INCO-750/ELGILOY)	10522
MB0160-050	CRES 21-6-9 BAR ANNEALED	10104
	CRES 21-6-9 FORGING ANNEALED	50759
	CRES 21-6-9 RINGS ANNEALED	50760
MB0170-014	BRAZE 81.5AU 16.5CU 2.0NI	10196
MB0170-019	BRAZE 72AU 22NI 6CR	10198
MB0170-036	BRAZE LTC 80/20 NI MATRIX	10199
MB0170-037	BRAZE 62.5AG 32.5CU 5NI	10200
MB0170-038	CB C129Y SHEET ANNEALED	30052
	CB C129Y STRIP ANNEALED	50698
MB0170-040	INCONEL 718 SHEET CEVM STA1900F	10331
	INCONEL 718 PLATE CEVM 1900F	50882
	INCONEL 718 STRIP CEVM ST1900F	50883
MB0170-041	INCONEL 718 BAR CEVM	10332
	INCONEL 718 FORGING CEVM	50881
MB0170-044	ELGILOY RC55 WIRE SPRING	10146
	ELGILOY RC55 STRIP SPRING	50842
MB0170-055	BE 2% BEO PLATE	50688
	BE 2% BEO BAR	50689
	BE 2% BEO FORGING	50690
	BE 2% BEO EXTRUSIONS	50691
MB0170-068	CB 752 SHEET ANNEALED	30051
	CB 752 STRIP ANNEALED	50704
MB0170-069	INCONEL 601 PLATE ANNEALED	50859
MB0170-071	INCONEL 718 SHEET ST1900	10126
	INCONEL 718 PLATE ST1900F	50886
	INCONEL 718 STRIP ST1900F	50887
MB0170-073	WELD WIRE AL 5356 UNCOATED	10162
	WELD WIRE AL 5556 UNCOATED	10163
	WELD WIRE TI CP UNCOATED	10164
	WELD WIRE 5AL 2.5SN UNCOATED	10165
	WELD WIRE ELI TI CP UNCOATED	10167
	WELD WIRE CRES 17-4PH	10170
	WELD WIRE CRES 14PH-8	10172
	WELD WIRE CRES 13PH-8	10173
	WELD WIRE CRES AM350 UNCOATED	10174
	WELD WIRE CRES 308 ELEC	10175
	WELD WIRE CRES 310 UNCOATED	10177
	WELD WIRE CRES 316 UNCOATED	10178
	WELD WIRE CRES 316 ELC	10179
	WELD WIRE CRES 321 UNCOATED	10180
	WELD WIRE CRES 21-6-9	10181
	WELD WIRE STEEL ER 502	10182
	WELD WIRE STEEL OXWELD 71	10183
	WELD WIRE STEEL 17-22AS	10184
MB0170-073	WELD WIRE AL 4043 UNCOATED	10185
	WELD WIRE STEEL 9NI 4CO 2C	10186
	WELD WIRE STEEL 18-7 MAR	10187
	WELD WIRE NI BASE HASTELLOY W	10188
	WELD WIRE NI BASE INCO 69	10191
	WELD WIRE NI BASE INCO 82	10192
	WELD WIRE NI BASE INCO 625	10193
	WELD WIRE CO BASE HAYNES 25	10195
	WELD WIRE CRES AM355 UNCOATED	10228
	WELD WIRE CRES 13-7 MO ELEC	10229
	WELD WIRE CRES A286 UNCOATED	10230
MB0170-073 UNC	WELD WIRE CRES 347	10176
MB0170-074	INCONEL 718 SHEET ST1750	10128
	INCONEL 718 PLATE ST1750F	50884
	INCONEL 718 STRIP ST1750F	50885
MB0170-075	INCONEL 718 BAR ST1750F	10129
	INCONEL 718 FORGING ST1750F	50874
	INCONEL 718 RING ST1750F	50875
MB0170-078	AL 2219-T62 SHEET	10015
	AL 6061-T6 SHEET	10022
	AL 7075-T73XX SHEET	10043
	AL 7075-T76X SHEET CLOSE TOLERANCE	10044
	AL 2219-T81 SHEET	10111
	AL 5052-H32 SHEET	10112
	AL 5052-H36 SHEET	10115
	AL 5456-H323 SHEET	10121
	AL 5456-H112 SHEET	10203
	AL 5456-H343 SHEET	10204
	AL 2024-T8X SHEET	10205
	AL 7178-T76XX SHEET CLOSE TOLERANCE	10238
	AL 5456-H321 SHEET	10255
	AL 2419-T8XX SHEET	10273
	AL 5052-H34 SHEET	50271
	AL 2024-T8X PLATE	50573
	AL 2219-T62 PLATE	50589
	AL 2219-T8X PLATE	50591
	AL 2419-T8XX PLATE	50596
	AL 5052-H32 PLATE	50607
	AL 5052-H34 PLATE	50608
	AL 5052-H36 PLATE	50609
	AL 5052-H38 PLATE	50610
	AL 5083-H32 PLATE	50618
	AL 5456-H112 PLATE	50623
	AL 5456-H321 PLATE	50624
	AL 5456-H323 PLATE	50625
	AL 5456-H343 PLATE	50626
	AL 6061-T4 PLATE	50642
	AL 6061-T6 PLATE	50645
	AL 7075-T7351 PLATE	50669
	AL 7075-T76X PLATE CLOSE TOLERANCE	50671
	AL 7178-T76XX PLATE CLOSE TOLERANCE	50675
MB0170-081	TITANIUM 6AL 4V FORGING HI-QUAL	10032
	TITANIUM 6AL 4V BAR DIFFUSION BOND	10398
MB0170-081 CL 2	TITANIUM 6AL 4V BAR HI-QUAL 55KSI	10066
MB0170-081S C2	TITANIUM 6AL 4V BAR	10069

MSFC-HDBK-527 REV F ■ 9999942 0005058 T ■

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
MB0170-082	TITANIUM 6AL 4V BAR DIFFUSION BOND	10398
MB0170-082S	TITANIUM 6AL 4V SHEET ANNEALED	10065
	TITANIUM 6AL 4V SHEET	10068
	TITANIUM 6AL 4V PLATE	50951
MB0170-083	AL 2419-T8XX PLATE	50596
MB0170-084	TITANIUM 3AL 2.5V TUBE	10061
MB0170-089	TITANIUM 6AL 4V FORGING HI-QUAL	10032
MB0170-089 S	TITANIUM 6AL 4V BAR HI-QUAL 55KSI	10066
MB0170-089S	TITANIUM 6AL 4V BAR	10069
MB0170-095	BRAZE 66NI 12MN 7SI 5CU (AMBRY930	10326
MB0170-097	TITANIUM 3AL 2.5V TUBE ANNEALED	10453
MB0170-098	AL 7075 FORGING HAND	10454
MB0170-100	TITANIUM 3AL 2.5V FOIL ANNEALED	10310
MB0170-102	ELGILOY RC55 STRIP SPRING	50842
MB0170-104 CL 1	CB C-103 BAR INGOT	10719
MB0170-104 CL 2	CB C-103 BAR INGOT	10719
ME261-0033	K-6 ALLOY PLATING NI PB CR	30118
MIL-A-12545	AL 6070 IMPACTS	51675
	AL 2014-O IMPACTS	52423
	AL 2014-T4 IMPACTS	52424
	AL 2014-T6 IMPACTS	52425
MIL-A-12545A	AL 7075-O IMPACTS	51495
	AL 7075-T6 IMPACTS	51496
	AL 7075-T73 IMPACTS	51503
MIL-A-12545C	AL 6061-O IMPACTS	51372
	AL 6061-F IMPACTS	51373
	AL 6061-T4 IMPACTS	51374
	AL 6061-T6 IMPACTS	51375
	AL 6061-T84 IMPACTS	51376
	AL 6061-H112 IMPACTS	51377
MIL-A-21180	AL A356.0-T61 CASTINGS	10053
	AL C355.0-T6 CASTING	10395
	AL 355.0 CASTING	10639
	AL A356.0-T6 CASTING INVESTMENT	50060
MIL-A-21180C	AL C355.0-T61 CASTINGS PERMANENT MOLD	52871
MIL-A-21180D	AL 357.0-F CASTINGS PERMANENT MOLD	10293
	AL A201.0-T7 CASTINGS	50980
	AL 354.0-T4 CASTINGS PERMANENT MOLD	50981
	AL 354.0-T6 CASTINGS PERMANENT MOLD	50982
	AL 354.0-T61 CASTINGS PERMANENT MOLD	50983
	AL 354.0-T62 CASTINGS PERMANENT MOLD	50984
	AL A357.0-T6 CASTINGS SAND	50985
	AL A357.0-T61 CASTINGS	50986
	AL A356.0-T6 CASTINGS	51045
	AL 359.0-T61 CASTINGS	51228
	AL A201.0-T7 CASTINGS SPECIAL MOLD	52937
	AL A201.0-T4 CASTINGS PERMANENT MOLD	52938
	AL A201.0-T4 CASTINGS SAND (WITH CHILLS)	52939
	AL A201.0-T7 CASTINGS PERMANENT MOLD	52940
	AL A201.0-T7 CASTINGS SAND	52941
	AL 354.0-T4 CASTINGS SPECIAL MOLD	52942
	AL 354.0-T4 CASTINGS SAND (WITH CHILLS)	52943
	AL 354.0-T6 CASTINGS SPECIAL MOLD	52944
	AL 354.0-T6 CASTINGS SAND (WITH CHILLS)	52945
	AL 354.0-T61 CASTINGS SPECIAL MOLD	52946
MIL-A-21180D	AL 354.0-T61 CASTINGS SAND (WITH CHILLS)	52947
	AL 354.0-T62 CASTINGS SPECIAL MOLD	52948
	AL 354.0-T62 CASTINGS SAND (WITH CHILLS)	52949
	AL A357.0-T6 CASTINGS PERMANENT MOLD	52951
	AL A357.0-T6 CASTINGS SPECIAL MOLD	52952
	AL A357.0-T61 CASTINGS SAND	52953
	AL A357.0-T61 CASTINGS PERMANENT MOLD	52954
	AL A357.0-T61 CASTINGS SPECIAL MOLD	52955
MIL-A-22771	AL 7075-T7352 FORGING	10048
	AL 2219-T852 FORGING	30106
	AL 7049-T73 FORGING HAND	51786
	AL 7049-T7352 FORGING HAND	51787
	AL 7049-T73 FORGING DIE	51788
	AL 2014-T6 FORGING DIE	52414
	AL 2014-T6 FORGING HAND	52416
	AL 2014-T652 FORGING HAND	52417
	AL 2014-T6 RINGS ROLLED	52418
	AL 2014-T652 RINGS ROLLED	52419
MIL-A-22771C	AL 7175-O FORGING HAND	50294
MIL-A-22771D	AL 2219-T852 FORGING HAND	10007
	AL 2219-T6 FORGING HAND	10014
	AL 7075-T6 FORGING	50101
	AL 2219-T6 FORGING DIE	50590
	AL 6151-T6 FORGING DIE	50989
	AL 6151-T6 RINGS ROLLED	50990
	AL 6151-T652 RINGS ROLLED	50991
	AL 2219-T6 RINGS ROLLED	51081
	AL 2618-F FORGING DIE	51143
	AL 2618-F FORGING HAND	51144
	AL 2618-F RINGS ROLLED	51145
	AL 2618-T61 FORGING DIE	51146
	AL 2618-T61 FORGING HAND	51147
	AL 6061-F FORGING DIE	51358
	AL 6061-T6 FORGING DIE	51359
	AL 6061-F FORGING HAND	51360
	AL 6061-T6 FORGING HAND	51361
	AL 6061-F RINGS ROLLED	51362
	AL 6061-T6 RINGS ROLLED	51363
	AL 6061-T651 RING ROLLED	51364
	AL 6061-T652 RINGS ROLLED	51365
	AL 7075-T73 FORGING DIE	51485
	AL 7075-T652 FORGING HAND	51486
	AL 7075-T73 FORGING HAND	51487
	AL 7075-T74 FORGING DIE	51488
	AL 7075-T74 FORGING HAND	51489
	AL 7075-T7452 FORGING HAND	51490
	AL 7075-T6 RINGS ROLLED	51491
	AL 7075-T652 RINGS ROLLED	51492
	AL 7175-T74 FORGING DIE	51543
	AL 7175-T74 FORGING HAND	51544
	AL 7175-T7452 FORGING HAND	51545
	AL 7175-T7452 FORGING DIE	51546
	AL 7175-T7454 FORGING DIE	51547
	AL 7050-T7452 FORGING HAND	52298
	AL 7050-T74 FORGING DIE	52299

MSFC-HDBK-527 REV F ■ 9999942 0005059 1 ■

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
MIL-A-22771D	AL 7075-T6 FORGING DIE	52928
	AL 7075-T6 FORGING HAND	52930
	AL 7075-T7352 FORGING HAND	52931
	AL 2618-T61 ROLLED RINGS	53025
MIL-A-46104	AL 6070-T6 ROD EXTRUDED	51667
	AL 6070-T62 ROD EXTRUDED	51668
	AL 6070-T6 BAR EXTRUDED	51669
	AL 6070-T62 BAR EXTRUDED	51670
	AL 6070-T6 SHAPES EXTRUDED	51671
	AL 6070-T62 SHAPES EXTRUDED	51672
	AL 6070-T6 TUBE EXTRUDED	51673
	AL 6070-T62 TUBE EXTRUDED	51674
MIL-A-52242	AL 7001-O ROD EXTRUDED	51630
	AL 7001-O BAR EXTRUDED	51631
	AL 7001-O SHAPES EXTRUDED	51632
	AL 7001-T6 ROD EXTRUDED	51633
	AL 7001-T6 BAR EXTRUDED	51634
	AL 7001-T6 SHAPES EXTRUDED	51635
	AL 7001-T62 ROD EXTRUDED	51636
	AL 7001-T62 BAR EXTRUDED	51637
	AL 7001-T62 SHAPES EXTRUDED	51638
	AL 7001-T6510 ROD EXTRUDED	51639
	AL 7001-T6510 BAR EXTRUDED	51640
	AL 7001-T6510 SHAPES EXTRUDED	51641
	AL 7001-T6511 ROD EXTRUDED	51642
	AL 7001-T6511 BAR EXTRUDED	51643
	AL 7001-T6511 SHAPES EXTRUDED	51644
MIL-A-81596	AL 5052-H191 FOIL	10033
	AL 5056-H39 FOIL	10261
	AL 5052-O FOIL	51954
	AL 5052-H19 FOIL	51955
MIL-A-8625	COATING ANODIC	10276
	COATING ANODIC T2	10277
	COATING ANODIC T3 HARD	10283
	COATING ANODIC T1	10640
MIL-B-20148	AL 4145 METAL BRAZING FILLER	51823
	AL 4047 METAL BRAZING FILLER	51832
MIL-B-20148 CL6	AL 6951 SHEET CLAD W/AL 4045	10309
MIL-B-6812	STEEL 4XXX BOLT >200 KSI	50135
MIL-C-14550	PLATING COPPER ELECTRODEPOSIT	10311
MIL-C-21768	COPPER ALLOY 210 (95%) SHEET	50144
	COPPER ALLOY 220 (90%) SHEET	50303
	COPPER ALLOY 210 (95%) STRIP	50830
	COPPER ALLOY 220 (90%) STRIP	50831
MIL-C-24111	CRES 17PH-4MO H1100 BAR	10471
MIL-C-24111 CL2	CRES 17PH-4MO H1025 FORGING	10073
	CRES 17PH-4MO H1025 ROD	50731
MIL-C-24111 CL3	CRES 17PH-4MO H1150 BAR	10074
	CRES 17PH-4MO H1150 FORGING	50739
MIL-C-26074	PLATING NICKEL ELECTROLESS	10046
MIL-C-27500	CABLE ELECTRICAL	50143
MIL-C-27599	CLAMP CABLE AL 2024-T4	50507
MIL-C-7438	AL 5056 HONEYCOMB CORE	50078
MIL-C-7438C	AL 5052 HONEYCOMB CORE	50128
MIL-C-7438F	AL 5052 CORE HONEYCOMB AEROWEB	50142
MIL-C-81021	BE-CU #175	10638
	BE-CU #10	50136
MIL-C-81562	PLATING CADMIUM ELECTRODEPOSIT	30082
MIL-C-8837	PLATING CADMIUM ELECTRODEPOSIT	30082
MIL-E-16053	WELD WIRE AL 2319	50074
	AL 2319 ELECTRODES WELDING	51812
	AL 4043 ELECTRODES WELDING	51814
	AL 5654-O ELECTRODES WELDING	51815
	AL 5554-O ELECTRODES WELDING	51820
	AL 5183-O ELECTRODES WELDING	51822
	AL 4145-O ELECTRODES WELDING	51825
	AL 5556-O ELECTRODES WELDING	51831
	AL 4047-T651 ELECTRODES WELDING	51834
	AL 4047 ELECTRODES WELDING	51835
	AL 5356-O ELECTRODES WELDING	51837
MIL-E-16053L	AL 2319-T351 ELECTRODES WELDING	51683
	AL 4043-T6 ELECTRODES WELDING	51686
	AL 4043-T651 ELECTRODES WELDING	51688
MIL-E-21562	WELD WIRE NI BASE INCO 82	10192
MIL-E-22200/2 C	WELD WIRE CRES 347	10176
MIL-E-23765	WELD WIRE STEEL AWS E 705-2	10357
MIL-E-46065	BRAZE NEYORO AU-PT-AG-CU ALLOY	10714
MIL-E-46065 COMP	PALINEY #7 COMP D	10608
MIL-F-14072	PLATING TIN	10312
MIL-F-55561	COPPER ALLOY 110 SHEET	10346
	COPPER SHAPES ANNEALED HARD TEMPER	50833
MIL-F-83142	TITANIUM 5AL 2.5SN BAR FORGING ANNEALED	10060
MIL-F-83142 CP6	TITANIUM 6AL 4V FORGING ANNEALED	10369
MIL-G-45204	PLATING GOLD	10328
MIL-I-11695	MAGNET ARMCO INGOT IRON	10269
MIL-I-23011 C2	MAGNET NI-FE ALLOY ROD	10442
MIL-I-23011 CL1	NICKEL ALLOY 53 (GLASS SEALING)	30069
MIL-I-23011 CL7	INVAR 36 BAR (GLASS SEALING)	10314
MIL-I-8846	CRES 303/304 BAR	10506
	CRES 303 WIRE	50774
MIL-M-45202	COATING ANODIC DOW 17	10743
MIL-M-46888	MAGNET ALNICO V. VI. VIII	10270
MIL-N-14411 C1	MAGNET NI-FE ALLOY SHEET	10215
MIL-N-14411 C1-2-	MAGNET NI-FE ALLOY BAR	50865
MIL-N-14411 C2	MAGNET NI-FE ALLOY SHEET	10215
MIL-N-14411 C3	MAGNET NI-FE ALLOY SHEET	10215
MIL-N-22840	MAGNET NI-FE ALLOY ROD	10442
MIL-N-46025	NICKEL BAR (ELECTRONIC)	10363
	NICKEL FL WIRE (ELECTRONIC)	50869
	NICKEL STRIP (ELECTRONIC)	50870
MIL-N-6840	INCONEL 600 SHEET ANNEALED	10134
	INCONEL 600 PLATE ANNEALED	50857
	INCONEL 600 STRIP ANNEALED	50858
MIL-N-7786	INCONEL X750 STRIP EXTRUDED	10136
	INCONEL X750 SHEET STA	10138
MIL-N-8550	INCONEL X750 BAR STA	10139
	INCONEL X750 FORGING STA	50852
	INCONEL X750 RINGS STA	50853
MIL-P-18317	PLATING NICKEL ELECTRODEPOSIT	10308
MIL-P-25995	AL 6063-T6 PIPE	52135

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005060 8 ■

SPECIFICATION	DESIGNATION	MATCD
MIL-P-25995	AL 3003-H112 PIPE	52993
	AL 3003-H18 PIPE	52994
MIL-P-25995B	AL 6061-T6 PIPE	51369
MIL-P-81728	SOLDER 70SN 30PB	10491
	PLATING TIN LEAD (ELEC-DEPOSIT	50108
MIL-R-46085	PLATING RHODIUM ELECTRODEPOSIT	30128
MIL-R-5031 CL6	WELD WIRE CRES 349	10323
MIL-R-5031/12	WELD WIRE NI BASE HASTELLOY W	10188
MIL-R-5674	AL 6053-T4 RIVET AND COLD HEADING	50120
MIL-S-12222	STEEL CARBON MOLYBDENUM 180-200KSI	10753
MIL-S-16598	INVAR 36 BAR (GLASS SEALING)	10314
MIL-S-17759	STEEL HNM BAR ANNEALED	53108
	STEEL HNM BAR ANNEALED AND AGED	53109
MIL-S-18729	STEEL 4130 SHEET 120-180 KSI	10108
	STEEL 4130 180-200KSI	50118
	STEEL 4130 PLATE 125-180 KSI	50912
MIL-S-22141	STEEL 4140 150KSI CASTING INVESTMENT	10153
	STEEL 4340 180KSI CASTING INVESTMENT	10154
	STEEL 4XXX CASTING INVESTMENT >200 KSI	30139
MIL-S-22499	BRASS SHIM STOCK >1/8HD COMP 2	10234
	STEEL SHIM STOCK COMP 4 MILD	10237
	AL SHIM STOCK (COMP 1)	10252
	CRES 18-8 SHIM STOCK	10606
MIL-S-23195	CRES 304 BAR ANNEALED	10351
	CRES 304 FORGING ANNEALED	50775
MIL-S-25043	CRES 17PH-7MO CH900 SHEET	10409
	CRES 17PH-7MO TH1100 SHEET	30020
	CRES 17PH-7MO RH900 SHEET	30077
	CRES 17PH-7MO CH900 STRIP	50750
	CRES 17PH-7MO PLATE CONDITION A	50752
	CRES 17PH-7MO STRIP CONDITION A	50753
	CRES 17PH-7MO STRIP CONDITION C	50754
	CRES 17PH-7MO RH900 PLATE	50755
	CRES 17PH-7MO RH900 STRIP	50756
	CRES 17PH-7MO TH1100 PLATE	50758
	CRES 17PH-7MO TH1050 STRIP	53324
	CRES 17PH-4MO PLATE TH1050	53325
	CRES 17PH-7MO RH950 STRIP	53332
	CRES 17PH-7MO RH950 PLATE	53333
	CRES 17PH-7MO PLATE CONDITION C	53334
	CRES 17PH-7MO CH900 PLATE	53335
MIL-S-4043	CRES 304L SHEET ANNEALED	10092
	CRES 304L PLATE ANNEALED	50790
	CRES 304L STRIP ANNEALED	50791
MIL-S-46084	STEEL ELEC M19 (3SI)	10490
MIL-S-46850	MARAGING STEEL 250>200KSI	10647
	MARAGING 18% STEEL >200KSI	30161
	MARAGING VASCO MAX 300 STEEL	30162
MIL-S-5000	STEEL 4340 BAR 180-200 KSI	10114
	STEEL 4XXX CASTING INVESTMENT >200 KSI	30139
	STEEL 4340 FORGING ANNEALED	50916
	STEEL 4340 FORGING 180-200 KSI	50922
MIL-S-5059	CRES 301 PLATE FULL HARD	10087
	CRES 301 SHEET ANNEALED 1/2 HARD 125KSI	10088
	CRES 302 SHEET	10262
MIL-S-5059	CRES 304 SHEET HARD	10263
	CRES 300 SERIES	10268
	CRES 302 PLATE ANNEALED THRU 1/2 HARD	10294
	CRES 302/304/316 FASTENRS ONLY	10315
	CRES 302/304 1/4 HARD	10349
	CRES 301/302 SHEET ANNEALED	10350
	CRES 304 PLATE ANNEALED THRU 1/2 HARD	10375
	CRES 300 SERIES NON-FREE MACH	10431
	CRES 302 STRIP 1/2 HARD	50365
	CRES 302 SHEET 1/2 HARD	50366
	CRES 301 SHEET 1/4 HARD	50515
	CRES 301 SHEET FULL HARD	50764
	CRES 301 STRIP FULL HARD	50765
	CRES 301 PLATE 1/4 HARD	50766
	CRES 301 STRIP 1/4 HARD	50767
	CRES 302 PLATE	50771
	CRES 302 STRIP	50772
	CRES 304 PLATE HARD	50782
	CRES 304 STRIP HARD	50783
	CRES 316 PLATE ANNEALED	50799
	CRES 316 STRIP ANNEALED	50800
MIL-S-5626	STEEL 4140 BAR <201 KSI	10122
	STEEL 4140 FORGING <201 KSI	50913
	STEEL 4140 RING <201 KSI	50914
MIL-S-6049	STEEL 8740 BAR >200 KSI	30096
MIL-S-6049A	STEEL 8740 BAR <200 KSI UTS	53169
	STEEL 8740 FORGING <200 KSI UTS	53170
MIL-S-6050	STEEL 8630 BAR >200 KSI	30133
MIL-S-6709	NITRALLOY 135MOD QUENCHED AND TEMPERED B	30063
	NITRALLOY 135MOD BAR HOT ROLLED	53241
	NITRALLOY 135MOD FORGING	53243
	NITRALLOY 135MOD FORGING STOCK	53244
	NITRALLOY 135MOD BAR QUENCHED & NITRIDED	53245
MIL-S-6721	CRES 321 SHEET ANNEALED	10097
	CRES 347 SHEET ANNEALED	10099
	CRES 300 SERIES	10268
	CRES 302/304/316 FASTENRS ONLY	10315
	CRES 321 FOIL	10380
	CRES 321 PLATE ANNEALED	50808
	CRES 321 STRIP ANNEALED	50809
	CRES 347 PLATE ANNEALED	50810
MIL-S-6758	STEEL 4130 BAR 125-180 KSI	10109
	STEEL 4130 FORGING 125-180 KSI	50911
MIL-S-7097	STEEL 1025 BAR ALL	52702
MIL-S-7108	STEEL HY-TUF BAR QUENCHED AND TEMPERED >	52638
MIL-S-7420	BRAZE 82AU 18NI	10119
	STEEL 52100 FORGING 180-200 KSI	50926
MIL-S-7420(E52100	STEEL 8620 BAR	10511
MIL-S-7720	CRES 302/304/316 FASTENRS ONLY	10315
	CRES 303 BAR FREE MACHINE	30080
MIL-S-7947	STEEL 1095 CONDITION 2 <200KSI SPRING	10299
MIL-S-7952	STEEL 1020 SHEET <180 KSI	50113
	STEEL 1025 SHEET COLD ROLLED	52699
	STEEL 1025 STRIP COLD ROLLED	52700
MIL-S-8503	STEEL 6150 BAR >200 KSI	10617

MSFC-HDBK-527 REV F ■ 9999942 0005061 T ■

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
MIL-S-867	CRES 347 CASTING ANNEALED	52774
MIL-S-8690(8620)	STEEL 8620 BAR	10511
MIL-S-8699	STEEL 4330V BAR >200 KSI	10110
	STEEL 4330V QUENCHED & TEMPERED 180-200	30165
MIL-S-8840	AM 350 SCT 850 SHEET	10207
	AM 350 SCT 1000 SHEET	10738
	AM 350 SCT 100 STRIP	50683
MIL-S-8844	STEEL 4XXX CASTING INVESTMENT >200 KSI	30139
	STEEL 4344 SHEET ANNEALED	50054
	STEEL 4340 BAR ANNEALED	50070
	STEEL 4340 FORGING ANNEALED	50916
	STEEL 300M BAR 270-300 KSI UTS	52620
	STEEL 300M FORGING 270-300 KSI UTS	52621
	STEEL 300M TUBE 270-300 KSI UTS	52622
	STEEL 300M CONSUMABLE VACUUM MELTED 270-	52623
	STEEL 300M MACHINED FORGING 270-300 KSI	52624
	STEEL 300M WIRE 270-300 KSI UTS	52625
	STEEL 300M BILLET 270-300 KSI UTS	52626
MIL-S-8844 C1	STEEL 4340 FORGING >200 KSI	50920
	STEEL 4340 TUBE >200 KSI	50921
MIL-S-8844 CL 1	STEEL 4340 BAR > 200KSI	10341
MIL-S-8949	STEEL D6AC SHEET PLATE >180 KSI	30110
MIL-STD-1276	WELD WIRE NI + CO	10700
MIL-STD-868 T1	PLATING NICKEL LOW EMBRITTLEMENT	50141
MIL-T-10727	PLATING TIN	10312
MIL-T-21014	TUNGSTEN SUPERDENSALLOY 180	30050
MIL-T-5066	STEEL 1025 TUBE COLD ROLLED	52701
MIL-T-50777	AL 2024-T3 TUBE DRAWN SEAMLESS	50554
	AL 2024-O TUBE DRAWN SEAMLESS	51127
	AL 2024-T42 TUBE DRAWN SEAMLESS	51128
MIL-T-6736	STEEL 4130 TUBE 125-180 KSI	10300
MIL-T-6845	CRES 304 TUBE 1/8 HARD	10436
MIL-T-7840	INCONEL 600 TUBE ANNEALED	10038
MIL-T-7928	COPPER TERMINAL LUG SPLICE	50114
MIL-T-81556	TITANIUM COMM PURE BAR 55KSI	10056
	TITANIUM 5AL 2.5SN BAR EXTRUDED ANNEALED	10059
	TITANIUM 6AL 4V BAR ROD EXTRUDED ANNEALE	10067
	TITANIUM 6AL 4V BAR EXTRUDED STA	10070
	TITANIUM 6AL 6V 2SN EXTRUSION	10414
	TITANIUM COMM PURE ROD 55KSI	50942
	TITANIUM COMM PURE SHAPES 55KSI	50943
	TITANIUM 5AL 2.5SN ROD EXTRUDED ANNEALED	50944
	TITANIUM 6AL 4V ROD EXTRUDED ANNEALED	50947
	TITANIUM 6AL 4V ROD EXTRUDED STA	50954
MIL-T-81915	TITANIUM 6AL 4V CASTING INVESTMENT 180-2	10729
MIL-T-8504	CRES 304 TUBE/PTFE ANNEALED	10413
MIL-T-8506	CRES 304 TUBE/PTFE ANNEALED	10413
MIL-T-8606	CRES 321 TUBE ANNEALED SEAMLESS	10101
	CRES 347 TUBE ANNEALED	10227
MIL-T-8808	CRES 321 TUBE ANNEALED SEAMLESS	10101
	CRES 347 TUBE ANNEALED	10227
MIL-T-8808 TY1	CRES 341 TUBE ANNEALED SEAMLESS	10102
MIL-T-9046	TITANIUM COMM PURE SHEET ANNEALED 55KSI	10054
	TITANIUM 5AL 2.5SN PLATE ANNEALED	10057
	TITANIUM 6AL 4V SHEET ANNEALED	10065
MIL-T-9046	TITANIUM 6AL 4V SHEET	10068
	TITANIUM 6AL 6V 2SN SHEET ANNEALED	10072
	TITANIUM COMM PURE STRIP ANNEALED 55 KSI	50940
	TITANIUM COMM PURE PLATE ANNEALED 55 KSI	50941
	TITANIUM 5AL 2.5SN STRIP ANNEALED	50945
	TITANIUM 5AL 2.5SN SHEET ANNEALED	50946
	TITANIUM 6AL 4V STRIP ANNEALED	50948
	TITANIUM 6AL 4V PLATE ANNEALED	50949
	TITANIUM 6AL 4V STRIP	50950
	TITANIUM 6AL 4V PLATE	50951
	TITANIUM 6AL 6V 2SN PLATE ANNEALED	50956
	TITANIUM 6AL 6V 2SN STRIP ANNEALED	50957
MIL-T-9047	TITANIUM COMM PURE BAR ANNEALED 55KSI	10055
	TITANIUM 5AL 2.5SN BAR FORGING ANNEALED	10058
	TITANIUM 5AL 2.5SN BAR FORGING ANNEALED	10060
	TITANIUM 6AL 4V BAR HI-QUAL 55KSI	10066
	TITANIUM 6AL 4V BAR	10069
	TITANIUM 6AL 6V 2SN BAR ANNEALED	10295
	TITANIUM 6AL 4V FORGING STOCK	10383
	TITANIUM 6AL 4V BAR ANNEALED 125KSI ELI	10438
	TITANIUM 6AL 6V 2SN FORGING ANNEALED	50955
MIL-V-83976	PLATING CADMIUM ELECTRODEPOSIT	30082
MIL-W-16878/11	COPPER WIRE AG PLATE SOFT OR ANN	10469
MIL-W-16878/13	COPPER WIRE AG PLATE SOFT OR ANN	10469
MIL-W-16878/4	COPPER WIRE AG PLATE SOFT OR ANN	10469
MIL-W-16878/5	COPPER WIRE AG PLATE SOFT OR ANN	10469
MIL-W-16878/6	COPPER WIRE AG PLATE SOFT OR ANN	10469
MIL-W-16878/8	WIRE COPPER TIN PLATED	10330
MIL-W-21632 CLB	CRES 300 SERIES WIRE	10514
MIL-W-25038/1B	COPPER WIRE NI ELECTRICAL CLAD	10642
MIL-W-25038/2B	COPPER WIRE NI ELECTRICAL CLAD	10642
MIL-W-52263	CRES 203EZ WIRE ANNEALED	53125
MIL-W-5424CP-B	CRES 300 SERIES WIRE	10514
MIL-W-5846	T/C ALLOY CHROMEL-ALUMEL WIRE	10666
MIL-W-585T2C105	COPPER WIRE FABRIC STEEL WELDED	50068
MIL-W-6712	AL 4043 WIRE SPRAY GUN	51687
MIL-W-83420CP-B	CRES 300 SERIES WIRE	10514
MIL-W-85/1	COPPER 100% PLATE ANNEALED	50837
MRC-MS988	COPPER 62CU CDA350 BRASS COPPER	10372
MS0135	HASTELLOY B BAR	30083
MS19069	STEEL 9NI 4CO (.30C) BAR 180-200 KSI	30088
MS51607	BRONZE MESH 40-50 MICRONS-FILTER	50103
MSFC-SPEC-145	CRES A286 95KSI YIELD	50069
MSO135	HASTELLOY B FORGING	50843
QQ-A-1876	AL 11XX FOIL ANNEALED	10348
	AL 1145-O FOIL	51699
	AL 1145-H19 FOIL	51700
	AL 1100-O FOIL	52004
	AL 1100-H19 FOIL	52005
QQ-A-200/10	AL 6066-O WIRE EXTRUDED	51839
	AL 6066-T4 WIRE EXTRUDED	51840
	AL 6066-T4510 WIRE EXTRUDED	51841
	AL 6066-T4511 WIRE EXTRUDED	51842
	AL 6066-T42 WIRE EXTRUDED	51843
	AL 6066-T6 WIRE EXTRUDED	51844

MSFC-HDBK-527 REV F 9999942 0005062 1

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
QQ-A-200/10	AL 6066-T6510 WIRE EXTRUDED	51845
	AL 6066-T6511 WIRE EXTRUDED	51846
	AL 6066-T62 WIRE EXTRUDED	51847
	AL 6066-O ROD EXTRUDED	51848
	AL 6066-T4 ROD EXTRUDED	51849
	AL 6066-T4510 ROD EXTRUDED	51850
	AL 6066-T4511 ROD EXTRUDED	51851
	AL 6066-T42 ROD EXTRUDED	51852
	AL 6066-T6 ROD EXTRUDED	51853
	AL 6066-T6510 ROD EXTRUDED	51854
	AL 6066-T6511 ROD EXTRUDED	51855
	AL 6066-T62 ROD EXTRUDED	51856
	AL 6066-O BAR EXTRUDED	51857
	AL 6066-T4 BAR EXTRUDED	51858
	AL 6066-T4510 BAR EXTRUDED	51859
	AL 6066-T4511 BAR EXTRUDED	51860
	AL 6066-T42 BAR EXTRUDED	51861
	AL 6066-T6 BAR EXTRUDED	51862
	AL 6066-T6510 BAR EXTRUDED	51863
	AL 6066-T6511 BAR EXTRUDED	51864
	AL 6066-T62 BAR EXTRUDED	51865
	AL 6066-O SHAPES EXTRUDED	51866
	AL 6066-T4 SHAPES EXTRUDED	51867
	AL 6066-T4510 SHAPES EXTRUDED	51868
	AL 6066-T4511 SHAPES EXTRUDED	51869
	AL 6066-T42 SHAPES EXTRUDED	51870
	AL 6066-T6 SHAPES EXTRUDED	51871
	AL 6066-T6510 SHAPES EXTRUDED	51872
	AL 6066-T6511 SHAPES EXTRUDED	51873
	AL 6066-T62 SHAPES EXTRUDED	51874
	AL 6066-O TUBE EXTRUDED	51875
	AL 6066-T4 TUBE EXTRUDED	51876
	AL 6066-T4510 TUBE EXTRUDED	51877
	AL 6066-T4511 TUBE EXTRUDED	51878
	AL 6066-T42 TUBE EXTRUDED	51879
	AL 6066-T6 TUBE EXTRUDED	51880
	AL 6066-T6510 TUBE EXTRUDED	51881
	AL 6066-T6511 TUBE EXTRUDED	51882
	AL 6066-T62 TUBE EXTRUDED	51883
QQ-A-200/11	AL 7075-T73511 BAR EXTRUDED	10421
	AL 7075-T62 BAR EXTRUDED	30122
	AL 7075-T73 TUBE EXTRUDED	50509
	AL 7075-T43 ROD EXTRUDED	50664
	AL 7075-T62 WIRE EXTRUDED	50665
	AL 7075-T73511 ROD EXTRUDED	50666
	AL 7075-T73511 WIRE EXTRUDED	50667
	AL 7075-T73 WIRE EXTRUDED	51431
	AL 7075-T73 ROD EXTRUDED	51432
	AL 7075-T73 BAR EXTRUDED	51433
	AL 7075-T73 SHAPES EXTRUDED	51434
	AL 7075-T73510 WIRE EXTRUDED	51435
	AL 7075-T73510 ROD EXTRUDED	51436
	AL 7075-T73510 BAR EXTRUDED	51437
	AL 7075-T73510 SHAPES EXTRUDED	51438
	AL 7075-T73510 TUBE EXTRUDED	51439
QQ-A-200/11	AL 7075-T73511 SHAPES EXTRUDED	51440
	AL 7075-O BAR EXTRUDED	51456
	AL 7075-O SHAPES EXTRUDED	51457
	AL 7075-O TUBE EXTRUDED	51458
	AL 7075-T6 WIRE EXTRUDED	51459
	AL 7075-T6 ROD EXTRUDED	51460
	AL 7075-T6 BAR EXTRUDED	51461
	AL 7075-T6 SHAPES EXTRUDED	51462
	AL 7075-T6 TUBE EXTRUDED	51463
	AL 7075-T62 ROD EXTRUDED	51464
	AL 7075-T62 SHAPES EXTRUDED	51465
	AL 7075-T62 TUBE EXTRUDED	51466
	AL 7075-T6510 WIRE EXTRUDED	51467
	AL 7075-T6510 ROD EXTRUDED	51468
	AL 7075-T6510 BAR EXTRUDED	51469
	AL 7075-T6510 SHAPES EXTRUDED	51470
	AL 7075-T6510 TUBE EXTRUDED	51471
	AL 7075-T6511 WIRE EXTRUDED	51472
	AL 7075-T6511 ROD EXTRUDED	51473
	AL 7075-T6511 BAR EXTRUDED	51474
	AL 7075-T6511 SHAPES EXTRUDED	51475
	AL 7075-T6511 TUBE EXTRUDED	51476
	AL 7075-T73511 TUBE EXTRUDED	52917
	AL 7075-O WIRE EXTRUDED	52918
	AL 7075-O ROD EXTRUDED	52919
QQ-A-200/13B	AL 7178-O WIRE EXTRUDED	52183
	AL 7178-O ROD EXTRUDED	52184
	AL 7178-O BAR EXTRUDED	52185
	AL 7178-O SHAPES EXTRUDED	52186
	AL 7178-O TUBE EXTRUDED	52187
	AL 7178-T6 WIRE EXTRUDED	52188
	AL 7178-T6 ROD EXTRUDED	52189
	AL 7178-T6 BAR EXTRUDED	52190
	AL 7178-T6 SHAPES EXTRUDED	52191
	AL 7178-T6 TUBE EXTRUDED	52192
	AL 7178-T6510 WIRE EXTRUDED	52193
	AL 7178-T6510 ROD EXTRUDED	52194
	AL 7178-T6510 BAR EXTRUDED	52195
	AL 7178-T6510 SHAPES EXTRUDED	52196
	AL 7178-T6510 TUBE EXTRUDED	52197
	AL 7178-T6511 WIRE EXTRUDED	52198
	AL 7178-T6511 ROD EXTRUDED	52199
	AL 7178-T6511 BAR EXTRUDED	52200
	AL 7178-T6511 SHAPES EXTRUDED	52201
	AL 7178-T6511 TUBE EXTRUDED	52202
	AL 7178-T62 WIRE EXTRUDED	52203
	AL 7178-T62 ROD EXTRUDED	52204
	AL 7178-T62 BAR EXTRUDED	52205
	AL 7178-T62 SHAPES EXTRUDED	52206
	AL 7178-T62 TUBE EXTRUDED	52207
QQ-A-200/14	AL 7178-T76 WIRE EXTRUDED	52208
	AL 7178-T76 ROD EXTRUDED	52209
	AL 7178-T76 BAR EXTRUDED	52210
	AL 7178-T76 SHAPES EXTRUDED	52211
	AL 7178-T76510 WIRE EXTRUDED	52213

MSFC-HDBK-527 REV F 9999942 0005063 3

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
QQ-A-200/14	AL 7178-T76510 ROD EXTRUDED	52214
	AL 7178-T76510 BAR EXTRUDED	52215
	AL 7178-T76510 SHAPES EXTRUDED	52216
	AL 7178-T76511 WIRE EXTRUDED	52218
	AL 7178-T76511 ROD EXTRUDED	52219
	AL 7178-T76511 BAR EXTRUDED	52220
	AL 7178-T76511 SHAPES EXTRUDED	52221
QQ-A-200/15	AL 7075-T76XXX EXTR EXFR RES	10041
	AL 7075-T76 WIRE EXTRUDED	51441
	AL 7075-T76 ROD EXTRUDED	51442
	AL 7075-T76 BAR EXTRUDED	51443
	AL 7075-T76 SHAPES EXTRUDED	51444
	AL 7075-T76 TUBE EXTRUDED	51445
	AL 7075-T76510 WIRE EXTRUDED	51446
	AL 7075-T76510 BAR EXTRUDED	51448
	AL 7075-T76510 SHAPES EXTRUDED	51449
	AL 7075-T76510 TUBE EXTRUDED	51450
	AL 7075-T76511 WIRE EXTRUDED	51451
	AL 7075-T76511 ROD EXTRUDED	51452
	AL 7075-T76511 BAR EXTRUDED	51453
	AL 7075-T76511 SHAPES EXTRUDED	51454
	AL 7075-T76511 TUBE EXTRUDED	51455
QQ-A-200/16A	AL 6061-T6 SHAPES EXTRUDED STRUCTURAL	51371
QQ-A-200/17	AL 6162-T5 WIRE EXTRUDED	52094
	AL 6162-T5 ROD EXTRUDED	52095
	AL 6162-T5 BAR EXTRUDED	52096
	AL 6162-T5 SHAPES EXTRUDED	52097
	AL 6162-T5 TUBE EXTRUDED	52098
	AL 6162-T5510 WIRE EXTRUDED	52099
	AL 6162-T5510 ROD EXTRUDED	52100
	AL 6162-T5510 BAR EXTRUDED	52101
	AL 6162-T5510 SHAPES EXTRUDED	52102
	AL 6162-T5510 TUBE EXTRUDED	52103
	AL 6162-T5511 WIRE EXTRUDED	52104
	AL 6162-T5511 ROD EXTRUDED	52105
	AL 6162-T5511 BAR EXTRUDED	52106
	AL 6162-T5511 SHAPES EXTRUDED	52107
	AL 6162-T5511 TUBE EXTRUDED	52108
	AL 6162-T6 WIRE EXTRUDED	52109
	AL 6162-T6 ROD EXTRUDED	52110
	AL 6162-T6 BAR EXTRUDED	52111
	AL 6162-T6 SHAPES EXTRUDED	52112
	AL 6162-T6 TUBE EXTRUDED	52113
	AL 6162-T6510 WIRE EXTRUDED	52114
	AL 6162-T6510 ROD EXTRUDED	52115
	AL 6162-T6510 BAR EXTRUDED	52116
	AL 6162-T6510 SHAPES EXTRUDED	52117
	AL 6162-T6510 TUBE EXTRUDED	52118
	AL 6162-T6511 WIRE EXTRUDED	52119
	AL 6162-T6511 ROD EXTRUDED	52120
	AL 6162-T6511 BAR EXTRUDED	52121
	AL 6162-T6511 SHAPES EXTRUDED	52122
	AL 6162-T6511 TUBE EXTRUDED	52123
QQ-A-200/1D	AL 3003-O ROD EXTRUDED	10385
	AL 3003-O TUBE EXTRUDED	10437
QQ-A-200/1D	AL 3003-O BAR EXTRUDED	50602
	AL 3003-O WIRE EXTRUDED	50603
	AL 3003-O SHAPES EXTRUDED	52985
	AL 3003-H112 WIRE EXTRUDED	52986
	AL 3003-H112 ROD EXTRUDED	52987
	AL 3003-H112 BAR EXTRUDED	52988
	AL 3003-H112 SHAPES EXTRUDED	52989
	AL 3003-H112 TUBE EXTRUDED	52990
QQ-A-200/2	AL 2014-O BAR EXTRUDED	52355
	AL 2014-T4 BAR EXTRUDED	52356
	AL 2014-T4510 BAR EXTRUDED	52357
	AL 2014-T4511 BAR EXTRUDED	52358
	AL 2014-T42 BAR EXTRUDED	52359
	AL 2014-T6 BAR EXTRUDED	52360
	AL 2014-T6510 BAR EXTRUDED	52361
	AL 2014-T6511 BAR EXTRUDED	52362
	AL 2014-T62 BAR EXTRUDED	52363
	AL 2014-O ROD EXTRUDED	52364
	AL 2014-T4 ROD EXTRUDED	52365
	AL 2014-T4510 ROD EXTRUDED	52366
	AL 2014-T4511 ROD EXTRUDED	52367
	AL 2014-T42 ROD EXTRUDED	52368
	AL 2014-T6 ROD EXTRUDED	52369
	AL 2014-T6510 ROD EXTRUDED	52370
	AL 2014-T6511 ROD EXTRUDED	52371
	AL 2014-T62 ROD EXTRUDED	52372
	AL 2014-O SHAPES EXTRUDED	52373
	AL 2014-T4 SHAPES EXTRUDED	52374
	AL 2014-T4510 SHAPES EXTRUDED	52375
	AL 2014-T4511 SHAPES EXTRUDED	52376
	AL 2014-T42 SHAPES EXTRUDED	52377
	AL 2014-T6 SHAPES EXTRUDED	52378
	AL 2014-T6510 SHAPES EXTRUDED	52379
	AL 2014-T6511 SHAPES EXTRUDED	52380
	AL 2014-T62 SHAPES EXTRUDED	52381
	AL 2014-O TUBE EXTRUDED	52382
	AL 2014-T4 TUBE EXTRUDED	52383
	AL 2014-T4510 TUBE EXTRUDED	52384
	AL 2014-T4511 TUBE EXTRUDED	52385
	AL 2014-T42 TUBE EXTRUDED	52386
	AL 2014-T6 TUBE EXTRUDED	52387
	AL 2014-T6510 TUBE EXTRUDED	52388
	AL 2014-T6511 TUBE EXTRUDED	52389
	AL 2014-T62 TUBE EXTRUDED	52390
	AL 2014-O WIRE EXTRUDED	52391
	AL 2014-T4 WIRE EXTRUDED	52392
	AL 2014-T4510 WIRE EXTRUDED	52393
	AL 2014-T4511 WIRE EXTRUDED	52394
	AL 2014-T42 WIRE EXTRUDED	52395
	AL 2014-T6 WIRE EXTRUDED	52396
	AL 2014-T6510 WIRE EXTRUDED	52397
	AL 2014-T6511 WIRE EXTRUDED	52398
	AL 2014-T62 WIRE EXTRUDED	52399
QQ-A-200/3	AL 2024-T8X BAR EXTRUDED	10004
	AL 2024-T6X BAR EXTRUDED	10291

MSFC-HDBK-527 REV F 9999942 0005064 5

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
QQ-A-200/3	AL 2024-T8510 BAR EXTRUDED	10420
	AL 2024-T4/T3511	30071
	AL 2024-T3 BAR EXTRUDED	30112
	AL 2024-T3 ROD EXTRUDED	50552
	AL 2024-T3 WIRE EXTRUDED	50553
	AL 2024-T4 TUBE	50562
	AL 2024-T6X ROD EXTRUDED	50568
	AL 2024-T6X WIRE EXTRUDED	50569
	AL 2024-T8510 ROD EXTRUDED	50577
	AL 2024-T8510 WIRE EXTRUDED	50578
	AL 2024-O WIRE EXTRUDED	51109
	AL 2024-T42 WIRE EXTRUDED	51110
	AL 2024-T81 WIRE EXTRUDED	51111
	AL 2024-O BAR EXTRUDED	51112
	AL 2024-T3510 BAR EXTRUDED	51113
	AL 2024-T3511 BAR EXTRUDED	51114
	AL 2024-T42 BAR EXTRUDED	51115
	AL 2024-O TUBE EXTRUDED	51117
	AL 2024-T3 TUBE EXTRUDED	51118
	AL 2024-T3510 TUBE EXTRUDED	51120
	AL 2024-T3511 TUBE EXTRUDED	51121
	AL 2024-T42 TUBE EXTRUDED	51122
	AL 2024-T81 TUBE EXTRUDED	51123
	AL 2024-T8510 TUBE EXTRUDED	51124
	AL 2024-T8511 TUBE EXTRUDED	51125
	AL 2024-O ROD EXTRUDED	51148
	AL 2024-T3510 ROD EXTRUDED	51150
	AL 2024-T3511 ROD EXTRUDED	51151
	AL 2024-T42 ROD EXTRUDED	51152
	AL 2024-T8511 ROD EXTRUDED	51153
	AL 2024-O SHAPES EXTRUDED	51155
	AL 2024-T3 SHAPES EXTRUDED	51156
	AL 2024-T3510 SHAPES EXTRUDED	51157
	AL 2024-T3511 SHAPES EXTRUDED	51158
	AL 2024-T42 SHAPES EXTRUDED	51159
	AL 2024-T8511 SHAPES EXTRUDED	51160
	AL 2024-T81 SHAPES EXTRUDED	53060
	AL 2024-T8510 SHAPES EXTRUDED	53065
	AL 2024-T8511 BAR EXTRUDED	53067
QQ-A-200/4D	AL 5083-H111 BAR EXTRUDED	10017
	AL 5083-H111 ROD EXTRUDED	50616
	AL 5083-H111 WIRE EXTRUDED	50617
	AL 5083-O BAR EXTRUDED	51239
	AL 5083-H112 BAR EXTRUDED	51240
	AL 5083-O ROD EXTRUDED	51241
	AL 5083-H112 ROD EXTRUDED	51242
	AL 5083-O WIRE EXTRUDED	51243
	AL 5083-H112 WIRE EXTRUDED	51244
	AL 5083-O TUBE EXTRUDED	51245
	AL 5083-H111 TUBE EXTRUDED	51246
	AL 5083-H112 TUBE EXTRUDED	51247
	AL 5083-O SHAPES EXTRUDED	51248
	AL 5083-H111 SHAPES EXTRUDED	51249
	AL 5083-H112 SHAPES EXTRUDED	51250
QQ-A-200/5D	AL 5086-O WIRE EXTRUDED	51005
QQ-A-200/5D	AL 5086-O ROD EXTRUDED	51006
	AL 5086-O BAR EXTRUDED	51007
	AL 5086-O SHAPES EXTRUDED	51008
	AL 5086-O TUBE EXTRUDED	51009
	AL 5086-H111 WIRE EXTRUDED	51010
	AL 5086-H111 ROD EXTRUDED	51011
	AL 5086-H111 BAR EXTRUDED	51012
	AL 5086-H111 SHAPES EXTRUDED	51013
	AL 5086-H111 TUBE EXTRUDED	51014
	AL 5086-H112 WIRE EXTRUDED	51015
	AL 5086-H112 ROD EXTRUDED	51016
	AL 5086-H112 BAR EXTRUDED	51017
	AL 5086-H112 SHAPES EXTRUDED	51018
	AL 5086-H112 TUBE EXTRUDED	51019
QQ-A-200/6	AL 5454-O WIRE EXTRUDED	51892
	AL 5454-O ROD EXTRUDED	51893
	AL 5454-O BAR EXTRUDED	51894
	AL 5454-O SHAPES EXTRUDED	51895
	AL 5454-O TUBE EXTRUDED	51896
	AL 5454-H111 WIRE EXTRUDED	51897
	AL 5454-H111 ROD EXTRUDED	51898
	AL 5454-H111 BAR EXTRUDED	51899
	AL 5454-H111 SHAPES EXTRUDED	51900
	AL 5454-H111 TUBE EXTRUDED	51901
	AL 5454-H112 WIRE EXTRUDED	51902
	AL 5454-H112 ROD EXTRUDED	51903
	AL 5454-H112 BAR EXTRUDED	51904
	AL 5454-H112 SHAPES EXTRUDED	51905
	AL 5454-H112 TUBE EXTRUDED	51906
QQ-A-200/7	AL 5456-H111 BAR EXTRUDED	10253
	AL 5456-H112 BAR EXTRUDED	10254
	AL 5456-H111 ROD EXTRUDED	50619
	AL 5456-H111 WIRE EXTRUDED	50620
	AL 5456-H112 ROD EXTRUDED	50621
	AL 5456-H112 WIRE EXTRUDED	50622
	AL 5456-O BAR EXTRUDED	52274
	AL 5456-O ROD EXTRUDED	52275
	AL 5456-O SHAPES EXTRUDED	52276
	AL 5456-H111 SHAPES EXTRUDED	52277
	AL 5456-H112 SHAPES EXTRUDED	52278
	AL 5456-O TUBE EXTRUDED	52279
	AL 5456-H111 TUBE EXTRUDED	52280
	AL 5456-H112 TUBE EXTRUDED	52281
	AL 5456-O WIRE EXTRUDED	52282
QQ-A-200/8	AL 6061-T4511 BAR EXTRUDED	10020
	AL 6061-T6 BAR EXTRUDED	10024
	AL 6061 BAR ANNEALED	10670
	AL 6061-T6511 BAR EXTRUDED	50299
	AL 6061-T4511 ROD EXTRUDED	50638
	AL 6061-T4511 WIRE EXTRUDED	50639
	AL 6061-T6 ROD EXTRUDED	50643
	AL 6061-T6 WIRE EXTRUDED	50644
	AL 6061-T6511 ROD EXTRUDED	50648
	AL 6061-T6511 WIRE EXTRUDED	50649
QQ-A-200/8F	AL 6061-T4 TUBE	10732

MSFC-HDBK-527 REV F ■ 9999942 0005065 7 ■

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
QQ-A-200/8F	AL 6061-O WIRE EXTRUDED	50653
	AL 6061-T4510 ROD EXTRUDED	51320
	AL 6061-T42 ROD EXTRUDED	51321
	AL 6061-T1 ROD EXTRUDED	51323
	AL 6061-T51 ROD EXTRUDED	51324
	AL 6061-T6510 ROD EXTRUDED	51325
	AL 6061-T1 BAR EXTRUDED	51326
	AL 6061-T4510 BAR EXTRUDED	51327
	AL 6061-T42 BAR EXTRUDED	51328
	AL 6061-T51 BAR EXTRUDED	51329
	AL 6061-T6510 BAR EXTRUDED	51330
	AL 6061-O SHAPES EXTRUDED	51331
	AL 6061-T6 SHAPES EXTRUDED	51332
	AL 6061-T62 SHAPES EXTRUDED	51333
	AL 6061-T1 SHAPES EXTRUDED	51334
	AL 6061-T4510 SHAPES EXTRUDED	51335
	AL 6061-T4511 SHAPES EXTRUDED	51336
	AL 6061-T42 SHAPES EXTRUDED	51337
	AL 6061-T51 SHAPES EXTRUDED	51338
	AL 6061-T6510 SHAPES EXTRUDED	51339
	AL 6061-T6511 SHAPES EXTRUDED	51340
	AL 6061-O TUBE EXTRUDED	51341
	AL 6061-T1 TUBE EXTRUDED	51342
	AL 6061-T4510 TUBE EXTRUDED	51343
	AL 6061-T4511 TUBE EXTRUDED	51344
	AL 6061-T42 TUBE EXTRUDED	51345
	AL 6061-T51 TUBE EXTRUDED	51346
	AL 6061-T6510 TUBE EXTRUDED	51347
	AL 6061-T6511 TUBE EXTRUDED	51348
	AL 6061-T6 TUBE EXTRUDED	51349
	AL 6061-T62 TUBE EXTRUDED	51350
	AL 6061-T1 WIRE EXTRUDED	51351
	AL 6061-T4 WIRE EXTRUDED	51352
	AL 6061-T4510 WIRE EXTRUDED	51353
	AL 6061-T42 WIRE EXTRUDED	51354
	AL 6061-T51 WIRE EXTRUDED	51355
	AL 6061-T62 WIRE EXTRUDED	51356
	AL 6061-T6510 WIRE EXTRUDED	51357
QQ-A-200/9	AL 6063-T42 BAR EXTRUDED	10394
	AL 6063-T52 BAR EXTRUDED	50279
	AL 6063-T42 ROD EXTRUDED	50655
	AL 6063-T42 WIRE EXTRUDED	50656
	AL 6063-T52 ROD EXTRUDED	50657
	AL 6063-T52 WIRE EXTRUDED	50658
	AL 6063-T6 BAR EXTRUDED	50970
	AL 6063-O WIRE EXTRUDED	52124
	AL 6063-O ROD EXTRUDED	52125
	AL 6063-O BAR EXTRUDED	52126
	AL 6063-O SHAPES EXTRUDED	52127
	AL 6063-O TUBE EXTRUDED	52128
	AL 6063-T5 WIRE EXTRUDED	52129
	AL 6063-T5 ROD EXTRUDED	52130
	AL 6063-T5 BAR EXTRUDED	52131
	AL 6063-T5 SHAPES EXTRUDED	52132
	AL 6063-T5 TUBE EXTRUDED	52133
QQ-A-200/9	AL 6063-T52 SHAPES EXTRUDED	52139
	AL 6063-T6 WIRE EXTRUDED	52140
	AL 6063-T6 ROD EXTRUDED	52141
	AL 6063-T6 SHAPES EXTRUDED	52143
	AL 6063-T52 TUBE EXTRUDED	52144
	AL 6063-T6 TUBE EXTRUDED	52145
	AL 6063-T1 WIRE EXTRUDED	52153
	AL 6063-T1 ROD EXTRUDED	52154
	AL 6063-T1 BAR EXTRUDED	52155
	AL 6063-T1 SHAPES EXTRUDED	52156
	AL 6063-T1 TUBE EXTRUDED	52157
	AL 6063-T4 WIRE EXTRUDED	52158
	AL 6063-T4 ROD EXTRUDED	52159
	AL 6063-T4 BAR EXTRUDED	52160
	AL 6063-T4 SHAPES EXTRUDED	52161
	AL 6063-T4 TUBE EXTRUDED	52162
	AL 6063-T42 SHAPES EXTRUDED	52165
	AL 6063-T42 TUBE EXTRUDED	52166
QQ-A-225/1	AL 1100 BAR	10217
	AL 1100 ROD	50532
	AL 1100 WIRE	50533
	AL 1100-O WIRE ROLLED	51962
	AL 1100-O ROD ROLLED	51963
	AL 1100-O BAR ROLLED	51964
	AL 1100-H12 WIRE ROLLED	51965
	AL 1100-H14 WIRE ROLLED	51966
	AL 1100-H16 WIRE ROLLED	51967
	AL 1100-H18 WIRE ROLLED	51968
	AL 1100-H112 WIRE ROLLED	51969
	AL 1100-H112 ROD ROLLED	51970
	AL 1100-H112 BAR ROLLED	51971
	AL 1100-O WIRE COLD FINISHED	52573
	AL 1100-O ROD COLD FINISHED	52574
	AL 1100-O BAR COLD FINISHED	52575
	AL 1100-H12 WIRE COLD FINISHED	52576
	AL 1100-H14 WIRE COLD FINISHED	52577
	AL 1100-H16 WIRE COLD FINISHED	52578
	AL 1100-H18 WIRE COLD FINISHED	52579
	AL 1100-H112 WIRE COLD FINISHED	52580
	AL 1100-H112 ROD COLD FINISHED	52581
	AL 1100-H112 BAR COLD FINISHED	52582
QQ-A-225/10	AL 6262 BAR	10507
	AL 6262-T9	10752
	AL 6262 ROD	50660
	AL 6262 WIRE	50661
	AL 6262-T6 WIRE ROLLED	52229
	AL 6262-T6 ROD ROLLED	52230
	AL 6262-T6 BAR ROLLED	52231
	AL 6262-T651 WIRE ROLLED	52232
	AL 6262-T651 ROD ROLLED	52233
	AL 6262-T651 BAR ROLLED	52234
	AL 6262-T9 WIRE ROLLED	52235
	AL 6262-T9 ROD ROLLED	52236
	AL 6262-T9 BAR ROLLED	52237
	AL 6262-T6 ROD EXTRUDED	52239

MSFC-HDBK-527 REV F 9999942 0005066 9

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
QQ-A-225/10	AL 6262-T6 WIRE COLD FINISHED	52850
	AL 6262-T6 ROD COLD FINISHED	52851
	AL 6262-T6 BAR COLD FINISHED	52852
	AL 6262-T651 WIRE COLD FINISHED	52853
	AL 6262-T651 ROD COLD FINISHED	52854
	AL 6262-T651 BAR COLD FINISHED	52855
	AL 6262-T9 WIRE COLD FINISHED	52856
	AL 6262-T9 ROD COLD FINISHED	52857
	AL 6062-T9 BAR COLD FINISHED	52858
QQ-A-225/2C	AL 3003-H112 BAR ROLLED	50130
	AL 3003-H112 ROD ROLLED	50597
	AL 3003-O WIRE ROLLED	50598
	AL 3003-O WIRE COLD FINISHED	52968
	AL 3003-O ROD ROLLED	52969
	AL 3003-O ROD COLD FINISHED	52970
	AL 3003-O BAR ROLLED	52971
	AL 3003-O BAR COLD FINISHED	52972
	AL 3003-H12 WIRE ROLLED	52973
	AL 3003-H12 WIRE COLD FINISHED	52974
	AL 3003-H14 WIRE ROLLED	52975
	AL 3003-H14 WIRE COLD FINISHED	52976
	AL 3003-H16 WIRE ROLLED	52977
	AL 3003-H16 WIRE COLD FINISHED	52978
	AL 3003-H18 WIRE ROLLED	52979
	AL 3003-H18 WIRE COLD FINISHED	52980
	AL 3003-H112 WIRE ROLLED	52981
	AL 3003-H112 WIRE COLD FINISHED	52982
	AL 3003-H112 ROD COLD FINISHED	52983
	AL 3003-H112 BAR COLD FINISHED	52984
QQ-A-225/3	AL 2011-T6 BAR	30135
	AL 2011-T3 BAR	50248
	AL 2011-T8 BAR	50249
	AL 2011-T3 WIRE	50536
	AL 2011-T6 ROD	50537
	AL 2011-T6 WIRE	50538
	AL 2011-T8 ROD	50539
	AL 2011-T8 WIRE	50540
	AL 2011-T3 ROD ROLLED	52009
	AL 2011-T4 ROD ROLLED	52010
	AL 2011-T451 ROD ROLLED	52011
	AL 2011-T8 ROD ROLLED	52012
	AL 2011-T3 BAR ROLLED	52013
	AL 2011-T4 BAR ROLLED	52014
	AL 2011-T451 BAR ROLLED	52015
	AL 2011-T8 BAR ROLLED	52016
	AL 2011-T3 WIRE ROLLED	52017
	AL 2011-T8 WIRE ROLLED	52018
	AL 2011-T3 ROD COLD FINISHED	52540
	AL 2011-T4 ROD COLD FINISHED	52541
	AL 2011-T451 ROD COLD FINISHED	52542
	AL 2011-T8 ROD COLD FINISHED	52543
	AL 2011-T3 BAR COLD FINISHED	52544
	AL 2011-T4 BAR COLD FINISHED	52545
	AL 2011-T451 BAR COLD FINISHED	52546
	AL 2011-T8 BAR COLD FINISHED	52547
QQ-A-225/3	AL 2011-T3 WIRE COLD FINISHED	52548
	AL 2011-T8 WIRE COLD FINISHED	52549
	AL 2011-T4 WIRE ROLLED	52550
	AL 2011-T451 WIRE ROLLED	52551
	AL 2011-T4 WIRE COLD FINISHED	52552
	AL 2011-T451 WIRE COLD FINISHED	52553
QQ-A-225/4	AL 2014-T6 BAR COLD FINISHED	50220
	AL 2014-O BAR ROLLED	51520
	AL 2014-T4 BAR ROLLED	51521
	AL 2014-T42 BAR ROLLED	51522
	AL 2014-T451 BAR ROLLED	51523
	AL 2014-T62 BAR ROLLED	51525
	AL 2014-T651 BAR ROLLED	51526
	AL 2014-O BAR COLD FINISHED	51527
	AL 2014-T4 BAR COLD FINISHED	51528
	AL 2014-T42 BAR COLD FINISHED	51529
	AL 2014-T451 BAR COLD FINISHED	51530
	AL 2014-T62 BAR COLD FINISHED	51532
	AL 2014-T651 BAR COLD FINISHED	51533
	AL 2014-O ROD ROLLED	52306
	AL 2014-T4 ROD ROLLED	52307
	AL 2014-T42 ROD ROLLED	52308
	AL 2014-T451 ROD ROLLED	52309
	AL 2014-T6 ROD ROLLED	52310
	AL 2014-T62 ROD ROLLED	52311
	AL 2014-T651 ROD ROLLED	52312
	AL 2014-O ROD COLD FINISHED	52313
	AL 2014-T4 ROD COLD FINISHED	52314
	AL 2014-T42 ROD COLD FINISHED	52315
	AL 2014-T451 ROD COLD FINISHED	52316
	AL 2014-T6 ROD COLD FINISHED	52317
	AL 2014-T62 ROD COLD FINISHED	52318
	AL 2014-T651 ROD COLD FINISHED	52319
	AL 2014-O WIRE ROLLED	52320
	AL 2014-T4 WIRE ROLLED	52321
	AL 2014-T42 WIRE ROLLED	52322
	AL 2014-T451 WIRE ROLLED	52323
	AL 2014-T6 WIRE ROLLED	52324
	AL 2014-T62 WIRE ROLLED	52325
	AL 2014-T651 WIRE ROLLED	52326
	AL 2014-O WIRE COLD FINISHED	52327
	AL 2014-T4 WIRE COLD FINISHED	52328
	AL 2014-T42 WIRE COLD FINISHED	52329
	AL 2014-T451 WIRE COLD FINISHED	52330
	AL 2014-T6 WIRE COLD FINISHED	52331
	AL 2014-T62 WIRE COLD FINISHED	52332
	AL 2014-T651 WIRE COLD FINISHED	52333
	AL 2014-O BAR DRAWN	52334
	AL 2014-T4 BAR DRAWN	52335
	AL 2014-T42 BAR DRAWN	52336
	AL 2014-T451 BAR DRAWN	52337
	AL 2014-T6 BAR DRAWN	52338
	AL 2014-T62 BAR DRAWN	52339
	AL 2014-T651 BAR DRAWN	52340
	AL 2014-O ROD DRAWN	52341

MSFC-HDBK-527 REV F ■ 9999942 0005067 0 ■

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
QQ-A-225/4	AL 2014-T4 ROD DRAWN	52342
	AL 2014-T42 ROD DRAWN	52343
	AL 2014-T451 ROD DRAWN	52344
	AL 2014-T6 ROD DRAWN	52345
	AL 2014-T62 ROD DRAWN	52346
	AL 2014-T651 ROD DRAWN	52347
	AL 2014-O WIRE DRAWN	52348
	AL 2014-T6 WIRE DRAWN	52349
	AL 2014-T42 WIRE DRAWN	52350
	AL 2014-T451 WIRE DRAWN	52351
	AL 2014-T62 WIRE DRAWN	52353
	AL 2014-T651 WIRE DRAWN	52354
	AL 2014-T4 WIRE DRAWN	53027
	AL 2014-T6 BAR ROLLED	53028
QQ-A-225/5E	AL 2017-O BAR ROLLED	30099
	AL 2017-T451 BAR ROLLED	50253
	AL 2017-T42 BAR ROLLED	50254
	AL 2017-T4 BAR ROLLED	50255
	AL 2017-T4 ROD ROLLED	50543
	AL 2017-T4 WIRE ROLLED	50544
	AL 2017-T42 ROD ROLLED	50545
	AL 2017-T42 WIRE ROLLED	50546
	AL 2017-T451 ROD ROLLED	50547
	AL 2017-O ROD ROLLED	50549
	AL 2017-O WIRE ROLLED	50550
	AL 2017-O BAR DRAWN	52809
	AL 2017-T4 BAR DRAWN	52810
	AL 2017-T42 BAR DRAWN	52811
	AL 2017-T451 BAR DRAWN	52812
	AL 2017-O BAR COLD FINISHED	52813
	AL 2017-T4 BAR COLD FINISHED	52814
	AL 2017-T42 BAR COLD FINISHED	52815
	AL 2017-T451 BAR COLD FINISHED	52816
	AL 2017-T42 ROD DRAWN	52817
	AL 2017-T451 ROD DRAWN	52818
	AL 2017-O ROD COLD FINISHED	52819
	AL 2017-T4 ROD COLD FINISHED	52820
	AL 2017-T42 ROD COLD FINISHED	52821
	AL 2017-T451 ROD COLD FINISHED	52822
	AL 2017-O WIRE DRAWN	52823
	AL 2017-T4 WIRE DRAWN	52824
	AL 2017-T42 WIRE DRAWN	52825
	AL 2017-O WIRE COLD FINISHED	52826
	AL 2017-T4 WIRE COLD FINISHED	52827
	AL 2017-T42 WIRE COLD FINISHED	52828
	AL 2017-O ROD DRAWN	52829
	AL 2017-T4 ROD DRAWN	52830
	AL 2017-T451 WIRE ROLLED	52831
QQ-A-225/6	AL 2024-T6 ROD ROLLED	10292
	AL 2024-T851 BAR ROLLED	10508
	AL 2024-O ROD ROLLED	10525
	AL 2024-O BAR ROLLED	10744
	AL 2024-T6 BAR COLD FINISHED	50221
	AL 2024-T4 BAR ROLLED	50267
	AL 2024-T4 ROD ROLLED	50560
QQ-A-225/6	AL 2024-T4 WIRE ROLLED	50561
	AL 2024-T6 WIRE COLD FINISHED	50566
	AL 2024-O WIRE ROLLED	50580
	AL 2024-T6 BAR ROLLED	51098
	AL 2024-T42 WIRE ROLLED	51099
	AL 2024-T42 ROD ROLLED	51100
	AL 2024-T42 BAR ROLLED	51101
	AL 2024-T62 WIRE ROLLED	51102
	AL 2024-T62 ROD ROLLED	51103
	AL 2024-T62 BAR ROLLED	51104
	AL 2024-T36 WIRE ROLLED	51105
	AL 2024-T351 BAR ROLLED	51106
	AL 2024-T351 ROD ROLLED	51107
	AL 2024-T851 ROD ROLLED	51108
	AL 2024-O BAR COLD FINISHED	53029
	AL 2024-O ROD COLD FINISHED	53032
	AL 2024-O WIRE COLD FINISHED	53033
	AL 2024-T351 BAR COLD FINISHED	53037
	AL 2024-T351 ROD COLD FINISHED	53038
	AL 2024-T36 WIRE COLD FINISHED	53045
	AL 2024-T4 BAR COLD FINISHED	53046
	AL 2024-T4 ROD COLD FINISHED	53047
	AL 2024-T4 WIRE COLD FINISHED	53048
	AL 2024-T42 BAR COLD FINISHED	53050
	AL 2024-T42 ROD COLD FINISHED	53051
	AL 2024-T42 WIRE COLD FINISHED	53052
	AL 2024-T6 ROD COLD FINISHED	53053
	AL 2024-T6 WIRE ROLLED	53054
	AL 2024-T62 BAR COLD FINISHED	53055
	AL 2024-T62 ROD COLD FINISHED	53056
	AL 2024-T62 WIRE COLD FINISHED	53057
	AL 2024-T851 ROD COLD FINISHED	53063
	AL 2024-T851 BAR COLD FINISHED	53064
QQ-A-225/7	AL 5052 BAR	10519
	AL 5052 ROD	50604
	AL 5052 WIRE	50605
	AL 5052-O WIRE ROLLED	51911
	AL 5052-O ROD ROLLED	51912
	AL 5052-H32 WIRE ROLLED	51914
	AL 5052-H34 WIRE ROLLED	51915
	AL 5052-H36 WIRE ROLLED	51916
	AL 5052-H38 WIRE ROLLED	51917
	AL 5052-F ROD ROLLED	51918
	AL 5052-F BAR ROLLED	51919
	AL 5052-H36 ROD DRAWN	51921
	AL 5052-H38 ROD DRAWN	51922
	AL 5052-O WIRE DRAWN	51923
	AL 5052-H32 WIRE DRAWN	51924
	AL 5052-H34 WIRE DRAWN	51925
	AL 5052-H36 WIRE DRAWN	51926
	AL 5052-H38 WIRE DRAWN	51927
	AL 5052-O ROD DRAWN	51928
	AL 5052-H32 ROD DRAWN	51929
	AL 5052-H34 ROD DRAWN	51930
	AL 5052-O BAR DRAWN	51931

MSFC-HDBK-527 REV F ■ 9999942 0005068 2 ■

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
QQ-A-225/7	AL 5052-H32 BAR DRAWN	51932
	AL 5052-H34 BAR DRAWN	51933
	AL 5052-H36 BAR DRAWN	51934
	AL 5052-H38 BAR DRAWN	51935
	AL 5052-O WIRE COLD FINISHED	52785
	AL 5052-O ROD COLD FINISHED	52786
	AL 5052-O BAR COLD FINISHED	52787
	AL 5052-H32 WIRE COLD FINISHED	52788
	AL 5052-H34 WIRE COLD FINISHED	52789
	AL 5052-H36 WIRE COLD FINISHED	52790
	AL 5052-H38 WIRE COLD FINISHED	52791
	AL 5052-F ROD COLD FINISHED	52792
	AL 5052-F BAR COLD FINISHED	52793
QQ-A-225/8	AL 6061-T6 BAR ROLLED	10023
	AL 6061 BAR	10218
	AL 6061-T4 WIRE COLD FINISHED	50633
	AL 6061-T4 SHAPES DRAWN	50634
	AL 6061-T6 SHAPE ROLLED	50650
	AL 6061-T6 ROD ROLLED	50651
QQ-A-225/8E	AL 6061-T4 BAR ROLLED	10019
	AL 6061-O BAR ROLLED	50269
	AL 6061-O ROD DRAWN	50632
	AL 6061-T4 ROD ROLLED	50640
	AL 6061-T4 SHAPES ROLLED	50641
	AL 6061-O ROD ROLLED	50652
	AL 6061-T42 BAR ROLLED	51294
	AL 6061-T62 BAR ROLLED	51295
	AL 6061-T6 BAR DRAWN	51296
	AL 6061-T651 BAR DRAWN	51297
	AL 6061-T6 BAR COLD FINISHED	51298
	AL 6061-T651 BAR COLD FINISHED	51299
	AL 6061-T42 ROD ROLLED	51300
	AL 6061-T62 ROD ROLLED	51301
	AL 6061-T6 ROD DRAWN	51302
	AL 6061-T62 ROD DRAWN	51303
	AL 6061-T651 ROD DRAWN	51304
	AL 6061-T6 ROD COLD FINISHED	51305
	AL 6061-T62 ROD COLD FINISHED	51306
	AL 6061-T651 ROD COLD FINISHED	51307
	AL 6061-T4 WIRE ROLLED	51308
	AL 6061-T42 WIRE ROLLED	51309
	AL 6061-T6 WIRE ROLLED	51310
	AL 6061-T62 WIRE	51311
	AL 6061-T4 WIRE DRAWN	51312
	AL 6061-T42 WIRE DRAWN	51313
	AL 6061-T6 WIRE DRAWN	51314
	AL 6061-T62 WIRE DRAWN	51315
	AL 6061-T42 SHAPES ROLLED	51316
	AL 6061-T62 SHAPES ROLLED	51317
	AL 6061-T6 SHAPES DRAWN	51318
	AL 6061-T651 SHAPES DRAWN	51319
	AL 6061-O SHAPES	51322
QQ-A-225/9	AL 7075-T7351 BAR ROLLED	10047
	AL 7075-T73XX ROD ROLLED DRAWN	50668
	AL 7075-O WIRE ROLLED	50674
QQ-A-225/9	AL 7075-O BAR ROLLED	51385
	AL 7075-O BAR COLD FINISHED	51386
	AL 7075-T6 WIRE ROLLED	51387
	AL 7075-T6 WIRE COLD FINISHED	51388
	AL 7075-T6 ROD ROLLED	51389
	AL 7075-T6 ROD COLD FINISHED	51390
	AL 7075-T6 BAR ROLLED	51391
	AL 7075-T6 BAR COLD FINISHED	51392
	AL 7075-T62 WIRE ROLLED	51393
	AL 7075-T62 WIRE COLD FINISHED	51394
	AL 7075-T62 ROD ROLLED	51395
	AL 7075-T62 ROD COLD FINISHED	51396
	AL 7075-T62 BAR ROLLED	51397
	AL 7075-T62 BAR COLD FINISHED	51398
	AL 7075-T651 WIRE ROLLED	51399
	AL 7075-T651 WIRE COLD FINISHED	51400
	AL 7075-T651 ROD ROLLED	51401
	AL 7075-T651 ROD COLD FINISHED	51402
	AL 7075-T651 BAR ROLLED	51403
	AL 7075-T651 BAR COLD FINISHED	51404
	AL 7075-T73 WIRE ROLLED	51405
	AL 7075-T73 WIRE COLD FINISHED	51406
	AL 7075-T73 ROD ROLLED	51407
	AL 7075-T73 ROD COLD FINISHED	51408
	AL 7075-T73 BAR ROLLED	51409
	AL 7075-T73 BAR COLD FINISHED	51410
	AL 7075-T7351 WIRE ROLLED	51411
	AL 7075-T7351 WIRE COLD FINISHED	51412
	AL 7075-T7351 ROD ROLLED	51413
	AL 7075-T7351 ROD COLD FINISHED	51414
	AL 7075-T7351 BAR COLD FINISHED	51415
	AL 7075-T6 WIRE DRAWN	51416
	AL 7075-T62 WIRE DRAWN	51417
	AL 7075-T651 WIRE DRAWN	51418
	AL 7075-T73 WIRE DRAWN	51419
	AL 7075-T7351 WIRE DRAWN	51420
	AL 7075-T6 ROD DRAWN	51421
	AL 7075-T62 ROD DRAWN	51422
	AL 7075-T651 ROD DRAWN	51423
	AL 7075-T73 ROD DRAWN	51424
	AL 7075-T7351 ROD DRAWN	51425
	AL 7075-O BAR DRAWN	51426
	AL 7075-T6 BAR DRAWN	51427
	AL 7075-T62 BAR DRAWN	51428
	AL 7075-T651 BAR DRAWN	51429
	AL 7075-T73 BAR DRAWN	51430
	AL 7075-O WIRE COLD FINISHED	52911
	AL 7075-O ROD ROLLED	52912
	AL 7075-O ROD COLD FINISHED	52913
	AL 7075-O WIRE DRAWN	52914
	AL 7075-O ROD DRAWN	52915
	AL 7075-T7351 BAR DRAWN	52916
QQ-A-22771D	AL 7075-T7352 FORGING DIE	52929
QQ-A-250/1	AL 1100-O SHEET	10279
	AL 1100 SHEET ANNEALED	10366

MSFC-HDBK-527 REV F ■ 9999942 0005069 4 ■

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
QQ-A-250/1	AL 1100 SHEET CLAD	50298
	AL 1100-O PLATE	50534
	AL 1100-H14 PLATE	50974
	AL 1100-H14 SHEET	50975
	AL 1100-H12 SHEET	51957
	AL 1100-H12 PLATE	51958
	AL 1100-H16 SHEET	51959
	AL 1100-H18 SHEET	51960
	AL 1100-H112 PLATE	51961
QQ-A-250/10	AL 5454-O SHEET	51885
	AL 5454-O PLATE	51886
	AL 5454-H32 SHEET	51887
	AL 5454-H32 PLATE	51888
	AL 5454-H34 SHEET	51889
	AL 5454-H34 PLATE	51890
	AL 5454-H112 PLATE	51891
QQ-A-250/11	AL 6061-T4 SHEET	10018
	AL 6061-T6 SHEET	10022
	AL 6061 SHEET ANNEALED	10325
	AL 6061-T651 SHEET	50278
	AL 6061 PLATE ANNEALED	50631
	AL 6061-T4 PLATE	50642
	AL 6061-T6 PLATE	50645
	AL 6061-T651 PLATE	50646
	AL 6061-T651 STRIP	50647
QQ-A-250/11F	AL 6061-O SHEET	50148
	AL 6061-O PLATE	50654
	AL 6061-F SHEET	51288
	AL 6061-T42 SHEET	51289
	AL 6061-T62 SHEET	51290
	AL 6061-F PLATE	51291
	AL 6061-T42 PLATE	51292
	AL 6061-T62 PLATE	51293
QQ-A-250/12	AL 7075-T6 SHEET	10028
	AL 7075-T73XX SHEET	10043
	AL 7075-T73 SHEET	50239
	AL 7075-T43 PLATE	50663
	AL 7075-T7351 PLATE	50669
	AL 7075-O SHEET	51378
	AL 7075-O PLATE	51379
	AL 7075-T62 SHEET	51380
	AL 7075-T62 PLATE	51381
	AL 7075-T651 PLATE	51382
QQ-A-250/13	AL 7075-T6 SHEET CLAD	10457
	AL 7075-T762 SHEET CLAD	50089
	AL 7075-T762 PLATE CLAD	50672
	AL 7075-O SHEET CLAD	52430
	AL 7075-T62 SHEET CLAD	52431
	AL 7075-O PLATE CLAD	52432
	AL 7075-T62 PLATE CLAD	52433
	AL 7075-T651 PLATE CLAD	52434
QQ-A-250/14D	AL 7178-O SHEET	52174
	AL 7178-O PLATE	52175
	AL 7178-T6 SHEET	52176
	AL 7178-T651 PLATE	52179
QQ-A-250/14D	AL 7178-T6 PLATE	52182
QQ-A-250/15	AL 7178-T6 SHEET CLAD	30158
	AL 7178-O SHEET CLAD	52475
	AL 7178-O PLATE CLAD	52476
	AL 7178-T6 PLATE CLAD	52477
	AL 7178-T62 SHEET CLAD	52478
	AL 7178-T62 PLATE CLAD	52479
	AL 7178-T651 PPLATE CLAD	52480
QQ-A-250/18	AL 7075-O SHEET ONE SIDE CLAD	52448
	AL 7075-T6 SHEET ONE SIDE CLAD	52449
	AL 7075-T62 SHEET ONE SIDE CLAD	52450
	AL 7075-O PLATE ONE SIDE CLAD	52451
	AL 7075-T62 PLATE ONE SIDE CLAD	52452
	AL 7075-T651 PLATE ONE SIDE CLAD	52453
QQ-A-250/2	AL 3003 STRIP	50599
QQ-A-250/21	AL 7178-T76XX SHEET CLOSE TOLERANCE	10238
	AL 7178-T76XX PLATE CLOSE TOLERANCE	50675
	AL 7178-T76 SHEET	52180
	AL 7178-T7651 PLATE	52181
QQ-A-250/22	AL 7178-T76 SHEET CLAD	52481
	AL 7178-T7651 PLATE CLAD	52482
QQ-A-250/24	AL 7075-T76X SHEET CLOSE TOLERANCE	10044
	AL 7075-T76X PLATE CLOSE TOLERANCE	50671
	AL 7075-T7651 PLATE	51384
	AL 7075-T76 SHEET	53026
QQ-A-250/25	AL 7075-T7651 SHEET CLAD	50090
	AL 7075-T76 SHEET CLAD	50091
	AL 7075-T7651 PLATE CLAD	50673
QQ-A-250/26	AL 7075-O SHEET CLAD W/7011	52465
	AL 7075-T6 SHEET CLAD W/7011	52466
	AL 7075-T62 SHEET CLAD W/7011	52467
	AL 7075-T76 SHEET CLAD W/7011	52468
	AL 7075-O PLATE CLAD W/7011	52469
	AL 7075-T62 PLATE CLAD W/7011	52470
	AL 7075-T651 PLATE CLAD W/7011	52471
	AL 7075-T7651 PLATE CLAD W/7011	52472
QQ-A-250/28	AL 7178-T6 SHEET CLAD W/7011	52614
	AL 7178-T62 SHEET CLAD W/7011	52615
	AL 7178-T651 PLATE CLAD W/7011	52616
	AL 7178-T76 SHEET CLAD W/7011	52617
	AL 7178-T7651 PLATE CLAD W/7011	52618
QQ-A-250/29	AL 2124-T851 PLATE	10006
QQ-A-250/2D	AL 3003-O SHEET	10282
	AL 3003-O PLATE	50600
	AL 3003-H12 SHEET	52961
	AL 3003-H12 PLATE	52962
	AL 3003-H14 SHEET	52963
	AL 3003-H14 PLATE	52964
	AL 3003-H16 SHEET	52965
	AL 3003-H18 SHEET	52966
	AL 3003-H112 PLATE	52967
QQ-A-250/3	AL 2014-T6 SHEET CLAD	10521
	AL 2014-T62 SHEET CLAD	50251
	AL 2014-T6 PLATE CLAD	50541
	AL 2014-T62 PLATE CLAD	50542

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005070 0 ■

SPECIFICATION	DESIGNATION	MATCD
QQ-A-250/30	AL 2219-T62 SHEET	10015
	AL 2219-T81 SHEET	10111
	AL 2219-T351 SHEET	10708
	AL 2219-T37 SHEET	50072
	AL 2219-T351 PLATE	50076
	AL 2219-T31 SHEET	50079
	AL 2219-T42 SHEET	50080
	AL 2219-T87 SHEET	50081
	AL 2219-T851 PLATE	50082
	AL 2219-T31 PLATE	50584
	AL 2219-T37 PLATE	50587
	AL 2219-T42 PLATE	50588
	AL 2219-T62 PLATE	50589
	AL 2219-T8X PLATE	50591
	AL 2219-T851 SHEET	50592
	AL 2219-T87 PLATE	50595
	AL 2219-O SHEET	51046
	AL 2219-O PLATE	51047
QQ-A-250/4	AL 2024-T8X SHEET	10205
	AL 2024-T62 SHEET	10210
	AL 2024-T81 SHEET	10750
	AL 2024-T351 SHEET	30055
	AL 2024-T3 SHEET	30111
	AL 2024-O SHEET	30140
	AL 2024-T4 SHEET	50268
	AL 2024-T3 PLATE	50556
	AL 2024-T351 PLATE	50558
	AL 2024-T62 PLATE	50570
	AL 2024-T8X PLATE	50573
	AL 2024-T81 PLATE	50575
	AL 2024-T851 PLATE	50973
	AL 2024-O PLATE	51090
	AL 2024-T361 SHEET	51091
	AL 2024-T361 PLATE	51092
	AL 2024-T861 SHEET	51093
	AL 2024-T861 PLATE	51094
	AL 2024-T72 SHEET	51095
	AL 2024-T42 SHEET	51096
	AL 2024-T42 PLATE	51097
QQ-A-250/5	AL 2024-O PLATE CLAD	10408
	AL 2024-T81 PLATE CLAD	50092
	AL 2024-T3 SHEET CLAD	50256
	AL 2024-T36 SHEET CLAD	50257
	AL 2024-T4 SHEET CLAD	50258
	AL 2024-T42 SHEET CLAD	50259
	AL 2024-T6 SHEET CLAD	50260
	AL 2024-T86 PLATE CLAD	50262
	AL 2024-T351 SHEET CLAD	50263
	AL 2024-T851 PLATE CLAD	50264
	AL 2024-F SHEET CLAD	50265
	AL 2024-F PLATE CLAD	50551
	AL 2024-T3 PLATE CLAD	50555
	AL 2024-T351 PLATE CLAD	50557
	AL 2024-T36 PLATE CLAD	50559
	AL 2024-T42 PLATE CLAD	50565
QQ-A-250/5	AL 2024-T6 PLATE CLAD	50567
	AL 2024-T81 SHEET CLAD	50574
	AL 2024-T851 SHEET CLAD	50576
	AL 2024-T86 SHEET CLAD	50579
	AL 2024-O SHEET CLAD	50581
	AL 2024-T361 SHEET CLAD	51203
	AL 2024-T361 PLATE CLAD	51204
	AL 2024-T62 SHEET CLAD	51205
	AL 2024-T62 PLATE CLAD	51206
	AL 2024-T72 SHEET CLAD	51207
	AL 2024-T861 SHEET CLAD	51208
	AL 2024-T861 PLATE CLAD	51209
QQ-A-250/6G	AL 5083-H32 SHEET	10016
	AL 5083-H32 PLATE	50618
	AL 5083-O SHEET	51232
	AL 5083-H321 SHEET	51233
	AL 5083-H323 SHEET	51234
	AL 5083-H343 SHEET	51235
	AL 5083-O PLATE	51236
	AL 5083-H321 PLATE	51237
	AL 5083-H112 PLATE	51238
QQ-A-250/7E	AL 5086-O SHEET	50993
	AL 5086-O PLATE	50994
	AL 5086-H32 SHEET	50995
	AL 5086-H32 PLATE	50996
	AL 5086-H34 SHEET	50997
	AL 5086-H34 PLATE	50998
	AL 5086-H36 SHEET	50999
	AL 5086-H38 SHEET	51000
	AL 5086-H112 SHEET	51001
	AL 5086-H112 PLATE	51002
	AL 5086-H116 SHEET	51003
	AL 5086-H116 PLATE	51004
QQ-A-250/8	AL 5052-H32 SHEET	10112
	AL 5052-H36 SHEET	10115
	AL 5052-O SHEET	50216
	AL 5052-H34 SHEET	50271
	AL 5052-H38 SHEET	50274
	AL 5052-H24 SHEET	50277
	AL 5052 SHEET ANNEALED	50296
	AL 5052-H24 PLATE	50606
	AL 5052-H32 PLATE	50607
	AL 5052-H34 PLATE	50608
	AL 5052-H36 PLATE	50609
	AL 5052-H38 PLATE	50610
	AL 5052-O PLATE	50611
	AL 5052-H112 PLATE	51956
QQ-A-250/9	AL 5456-H323 SHEET	10121
	AL 5456-H112 SHEET	10203
	AL 5456-H343 SHEET	10204
	AL 5456-H321 SHEET	10255
	AL 5456-H112 PLATE	50623
	AL 5456-H321 PLATE	50624
	AL 5456-H323 PLATE	50625
	AL 5456-H343 PLATE	50626

MSFC-HDBK-527 REV F 9999942 0005071 2

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
QQ-A-250/9	AL 5456-O PLATE	52270
	AL 5456-H116 PLATE	52271
	AL 5456-O SHEET	52272
	AL 5456-H116 SHEET	52273
QQ-A-367	AL 7075-T7352 FORGING	10048
	AL 6061-T652 FORGING	10337
	AL 2219-T852 FORGING	30106
	AL 2219-T352 FORGING	50073
	AL 7075-T6 FORGING	50101
	AL 2025-T6 FORGING DIE	51139
	AL 2025-T6 FORGING STOCK	51141
	AL 7049-T73 FORGING HAND	51786
	AL 7049-T7352 FORGING HAND	51787
	AL 7049-T73 FORGING DIE	51788
	AL 2014-T6 FORGING DIE	52414
	AL 2014-T4 FORGING DIE	52415
	AL 2014-T6 FORGING HAND	52416
	AL 2014-T652 FORGING HAND	52417
QQ-A-367H	AL 2219-T852 FORGING HAND	10007
	AL 2219-T6 FORGING HAND	10014
	AL 2219-T6 FORGING DIE	50590
	AL 6151-T6 FORGING DIE	50989
	AL 2618-T61 FORGING DIE	51146
	AL 2618-T61 FORGING HAND	51147
	AL 2218-F FORGING DIE	51190
	AL 2218-T61 FORGING DIE	51191
	AL 2218-T72 FORGING DIE	51192
	AL 5083-H111 FORGING DIE	51251
	AL 5083-H112 FORGING DIE	51252
	AL 5083-H111 FORGING HAND	51253
	AL 5083-H112 FORGING HAND	51254
	AL 6061-T6 FORGING DIE	51359
	AL 6061-T6 FORGING HAND	51361
	AL 6061-T61 FORGING HAND	51370
	AL 7075-T73 FORGING DIE	51485
	AL 7075-T652 FORGING HAND	51486
	AL 7075-T73 FORGING HAND	51487
	AL 2018-T61 FORGING DIE	51593
	AL 4032-T6 FORGING DIE	51826
	AL 6066-T6 FORGING DIE	51884
	AL 7075-T6 FORGING DIE	52928
	AL 7075-T7352 FORGING DIE	52929
	AL 7075-T6 FORGING HAND	52930
	AL 7075-T7352 FORGING HAND	52931
	AL 2219-T6 FORGING	53072
QQ-A-367V	AL 7049-T73 FORGING	10026
QQ-A-371	AL 43 CASTING INGOT	10641
QQ-A-430	AL 1100 BAR	10217
	AL 2117-H13 ROD	10224
	AL 2117-T4 ROD	10335
	AL 5556	50240
	AL 5052 RIVET	50501
	AL 1100 ROD	50532
	AL 1100 WIRE	50533
	AL 2117-H13 WIRE RIVET AND COLD HEADING	50582

SPECIFICATION	DESIGNATION	MATCD
QQ-A-430	AL 2024-O WIRE RIVET AND COLD HEADING	51129
	AL 2024-H13 WIRE RIVET AND COLD HEADING	51130
	AL 2024-H23 WIRE RIVET AND COLD HEADING	51132
	AL 2024-O ROD RIVET AND COLD HEADING	51133
	AL 2024-H13 ROD RIVET AND COLD HEADING	51134
	AL 2024-H23 ROD RIVET AND COLD HEADING	51136
QQ-A-430C	AL 6061-H13 WIRE	50119
	AL 2117-T4 WIRE RIVET AND COLD HEADING	50583
	AL 6061-H13 ROD RIVET AND COLD HEADING	50635
	AL 6061-H13 WIRE RIVET AND COLD HEADING	50636
	AL 2219-H13 WIRE RIVET AND COLD HEADING	51082
	AL 2219-H13 ROD RIVET AND COLD HEADING	51084
	AL 2219-O WIRE RIVET AND COLD HEADING	51086
	AL 2219-H23 WIRE RIVET AND COLD HEADING	51087
	AL 2219-O ROD RIVET AND COLD HEADING	51088
	AL 2219-H23 ROD RIVET AND COLD HEADING	51089
	AL 5056-H32 WIRE RIVET AND COLD HEADING	51210
	AL 5056-H32 ROD RIVET AND COLD HEADING	51211
	AL 5056-H22 WIRE RIVET AND COLD HEADING	51212
	AL 5056-H22 ROD RIVET AND COLD HEADING	51213
	AL 6061-H23 WIRE RIVET AND COLD HEADING	51281
	AL 6061-H23 ROD RIVET AND COLD HEADING	51282
	AL 7075-H13 WIRE RIVET AND COLD HEADING	51497
	AL 7075-H13 ROD RIVET AND COLD HEADING	51498
	AL 7075-H23 WIRE RIVET AND COLD HEADING	51501
	AL 7075-H23 ROD RIVET AND COLD HEADING	51502
	AL 5005-O WIRE RIVET AND COLD HEADING	51662
	AL 5005-O ROD RIVET AND COLD HEADING	51663
	AL 5005-H32 WIRE RIVET AND COLD HEADING	51664
	AL 5005-H32 ROD RIVET AND COLD HEADING	51665
	AL 6053-O WIRE RIVET AND COLD HEADING	51693
	AL 6053-O ROD RIVET AND COLD HEADING	51694
	AL 6053-H13 WIRE RIVET AND COLD HEADING	51695
	AL 6053-H13 ROD RIVET AND COLD HEADING	51696
	AL 6053-H23 WIRE RIVET AND COLD HEADING	51697
	AL 6053-H23 ROD RIVET AND COLD HEADING	51698
	AL 2117-O WIRE RIVET AND COLD HEADING	51766
	AL 2117-O ROD RIVET AND COLD HEADING	51767
	AL 2117-H15 WIRE RIVET AND COLD HEADING	51768
	AL 2117-H15 ROD RIVET AND COLD HEADING	51769
	AL 2117-H25 WIRE RIVET AND COLD HEADING	51770
	AL 2117-H25 ROD RIVET AND COLD HEADING	51771
	AL 2117-H23 ROD RIVET AND COLD HEADING	51772
	AL 5052-O WIRE RIVET AND COLD HEADING	51948
	AL 5052-H32 WIRE RIVET AND COLD HEADING	51949
	AL 5052-O ROD RIVET AND COLD HEADING	51950
	AL 5052-H32 ROD RIVET AND COLD HEADING	51951
	AL 5052-H22 WIRE RIVET	51952
	AL 5052-H22 ROD RIVET	51953
	AL 1100-O WIRE RIVET AND COLD HEADING	51997
	AL 1100-H14 WIRE RIVET AND COLD HEADING	51998
	AL 1100-O ROD RIVET AND COLD HEADING	51999
	AL 1100-H14 ROD RIVET AND COLD HEADING	52000
	AL 1100-H24 WIRE RIVET AND COLD HEADING	52001
	AL 1100-H24 ROD RIVET AND COLD HEADING	52002

MSFC-HDBK-527 REV F 9999942 0005072 4

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
QQ-A-430C	AL 7050-O WIRE RIVET AND COLD HEADING	52300
	AL 7050-H13 WIRE RIVET AND COLD HEADING	52301
	AL 7050-O ROD RIVET AND COLD HEADING	52302
	AL 7050-H13 ROD RIVET AND COLD HEADING	52303
	AL 7075-O RIVET AND WIRE COLD HEADING	52909
	AL 7075-O RIVET AND ROD COLD HEADING	52910
	AL 3003-O RIVET AND WIRE COLD HEADING	53017
	AL 3003-O RIVET AND ROD COLD HEADING	53018
	AL 3003-H14 RIVET AND WIRE COLD HEADING	53019
	AL 3003-H14 RIVET AND ROD COLD HEADING	53020
	AL 3003-H24 RIVET AND WIRE COLD HEADING	53022
	AL 3003-H24 RIVET AND ROD COLD HEADING	53023
	AL 2117-H13 RIVET AND ROD COLD HEADING	53070
	AL 2117-T4 RIVET AND ROD COLD HEADING	53071
QQ-A-591	AL A380 CASTINGS DIE	10396
	AL A360-F CASTINGS DIE	10613
QQ-A-591 CP-380	AL 380 CASTINGS	10636
QQ-A-596	AL 356.0-T51 CASTINGS PERMANENT MOLD	10050
	AL 356.0-T6 CASTINGS	10517
	AL 356.0-T6 CASTINGS PERMANENT MOLD	51226
	AL 355.0-T6 CASTINGS PERMAMENT MOLD	51557
	AL 355.0-T71 CASTINGS PERMANENT MOLD	51558
QQ-A-601	AL 356.0-O CASTINGS SAND	10051
	AL 356.0-T6 CASTINGS	10517
	AL 535-O CASTINGS SAND	50094
	AL 356.0-T6 CASTINGS SAND	50516
	AL 355.0-T71 CASTINGS SAND	51559
	AL 355.0-T6 CASTINGS SAND	51560
	AL 355.0-T51 CASTINGS SAND	51561
QQ-A-601F	AL 520.0-T4 CASTINGS SAND	51137
	AL 712.0-T5 CASTINGS SAND	51138
QQ-B-575	WIRE COPPER TIN PLATED	10330
QQ-B-613	BRASS,ALL FORM	10321
QQ-B-626	BRASS,ALL FORM	10321
	BRASS BAR	50310
	BRASS STRIP	50692
QQ-B-637	BRASS,ALL FORM	10321
QQ-B-654	BRAZE 45 AG 15 CU 16 ZN 24 CD	10364
	BRAZE 50AG 15CU 16ZN 20CD	10710
QQ-B-654 BAG-13	BRAZE 54AG 40CU 5ZN 1NI	10624
	BRAZE 56AG 42CU 2NI	10650
QQ-B-654 BAG-7	BRAZE 56AG 22CU 17ZN 5SN	10458
QQ-B-654 BAG-9	BRAZE 65AG 20CU 15ZN	10429
QQ-B-654 CL III	BRAZE AG15 80CU 5P	10244
QQ-B-654 GR-0	BRAZE 20AG 45CU 35ZN ALLOY 202	10462
QQ-B-655	AL 4343 METAL BRAZING FILLER	10672
	AL 4045 METAL BRAZING FILLER	51202
	AL 4145 METAL BRAZING FILLER	51823
	AL 4047 METAL BRAZING FILLER	51832
QQ-B-750	BRONZE PHOSPHOR-ALL FORMS	10322
	BRONZE PLATE	50694
	BRONZE SHEET	50695
	BRONZE STRIP	50696
	BRONZE WIRE	50697
QQ-B-825	COPPER BAR BUS TYPE 1	10317
QQ-B-825	COPPER ROD BUS TYPE 1	50834
	COPPER SHAPES BUS TYPE 1	50835
	COPPER SHAPES	50836
QQ-C-320	PLATING CHROMIUM CLASS 2	10275
QQ-C-390	AL BRONZE #630 ROD 110 KSI	10257
	BRONZE PHOSPHOR SAE 660	10360
	BE-CU CASTING	10467
QQ-C-390 ALY E7	BRONZE PHOSPHOR SAE 660	10360
QQ-C-465	AL BRONZE #606 FORGING 70 KSI	10329
	AL BRONZE #637	10410
	AL BRONZE #614 FORGING 70 KSI	50677
	AL BRONZE #642 FORGING 70 KSI	50679
	AL BRONZE #639	50712
QQ-C-501	COPPER BAR ANNEALED HARD TEMPER	10333
	COPPER ROD ANNEALED HARD TEMPER	50832
	COPPER SHAPES ANNEALED HARD TEMPER	50833
QQ-C-502	BRAZE COPPER FLAT RODS	10248
	COPPER BAR ANNEALED HARD TEMPER	10333
	COPPER RODS	10501
	BRAZE COPPER FLAT SHAPES	50693
	COPPER SHAPES	50836
QQ-C-504	COPPER RODS	10501
QQ-C-530	BE-CU #173 BAR	10271
	BE-CU #173 ROD	50961
	BE-CU #173 WIRE	50962
QQ-C-533	BE-CU #172 WIRE CONDITION A	10256
	BE-CU #170	50304
QQ-C-576	COPPER BAR ANNEALED HARD TEMPER	10333
	COPPER RODS	10501
	COPPER ROD ANNEALED HARD TEMPER	50832
	COPPER SHAPES ANNEALED HARD TEMPER	50833
	COPPER SHAPES	50836
QQ-C-585	COPPER 65 18NI 17ZN ALLOY 752	10715
QQ-C-591	COPPER SILICON-BRONZE ALLOY # 655	10698
QQ-L-171	LEAD ALLOY 6.5SB .5SN CASTING	30141
QQ-N-281	MONEL 400 67NI 30CU WIRE ANNEALED	10222
QQ-N-286	MONEL K-500 ALLOY	10740
	NI-AL-FE-CU ALLOY	10742
QQ-N-290	PLATING NICKEL ELECTRODEPOSIT	10308
QQ-P-416	PLATING CADMIUM	50124
QQ-P-416 TY2	PLATING CADMIUM ELECTRODEPOSIT	30082
QQ-P-428	PLATINUM-COBALT ALLOY	10703
QQ-R-175 COMP D	WIRE 60NI-16CR-24FE ELECTRICAL	10680
QQ-R-566	WELD WIRE AL 2319	50074
	AL 2319 ROD WELDING	51811
	AL 2319 ELECTRODES WELDING	51812
	AL 4043 ROD WELDING	51813
	AL 4043 ELECTRODES WELDING	51814
	AL 5654 ELECTRODES WELDING	51816
	AL 5654 WIRE WELDING	51817
	AL 5554 ROD WELDING	51818
	AL 5554 ELECTRODES WELDING	51819
	AL 5183 ROD WELDING	51821
	AL 4145 ROD WELDING	51824
	AL 5556 ROD WELDING	51829

MSFC-HDBK-527 REV F ■ 9999942 0005073 6 ■

Information Handling Services, 2000

SPECIFICATION	DESIGNATION	MATCD
QQ-R-566	AL 5556 ELECTRODES WELDING	51830
	AL 4047 ROD WELDING	51833
	AL 4047 ELECTRODES WELDING	51835
	AL 5356 ROD WELDING	51836
	AL 5183 ELECTRODES WELDING	53077
	AL 5356 ELECTRODES WELDING	53078
	AL 4145 ELECTRODES WELDING	53085
QQ-R-566 CL 1	WELD WIRE AL 4043 UNCOATED	10185
QQ-S-365	PLATING SILVER	10039
	PLATING SILVER FASTENERS ONLY	10281
QQ-S-561 CL5	BRAZE 50AG 16CU 15ZN 3NI	10728
QQ-S-571	SOLDER SN 50/60/62/63	10079
	SOLDER SN 40 WRAP 4	10206
	SOLDER 1.5% SILVER	10338
	SOLDER 96SN	10448
	SOLDER 5SB	10449
	SOLDER SN 10	10626
	SOLDER 5.5AG	10654
	SOLDER SN 20	10683
	SOLDER 5SN 95PB	10690
	SOLDER SN 60 PB 40	50231
QQ-S-630	STEEL 1010 TO 1040	10359
QQ-S-631	STEEL 1010 TO 1040	10359
QQ-S-633	STEEL 1010 TO 1040	10359
QQ-S-634	STEEL 1010 TO 1040	10359
QQ-S-637	STEEL 1010 TO 1040	10359
QQ-S-698	STEEL SHEET LOW CARBON 180-200 KSI	10687
	STEEL 1020 SHEET <180 KSI	50113
	STEEL 1009-1050 <180 KSI	50131
	STEEL 1020 PLATE <180 KSI	50901
	STEEL 1025 SHEET <180 KSI	50902
	STEEL 1025 PLATE <180 KSI	50903
QQ-S-741	STEEL SHEET LOW CARBON 180-200 KSI	10687
	STEEL CARBON RC 29-33	10720
QQ-S-763	CRES 316L BAR ANNEALED	10083
	CRES 302 BAR COLD DRAWN 100KSI	10089
	CRES 304 BAR CONDITION B	10091
	CRES 321 BAR ANNEALED	10098
	CRES 304L ROD ANNEALED	10306
	CRES 302/304/316 FASTENRS ONLY	10315
	CRES 304L WIRE SCREEN	10318
	CRES 302/304 FASTENER ONLY	10334
	CRES 305 BAR ANNEALED	10336
	CRES 304 BAR ANNEALED	10351
	CRES 316 BAR CONDITION A	10370
	CRES 302 BAR	10382
	CRES 302 WIRE SPRING TEMPER B	10391
	CRES 300 SERIES NON-FREE MACH	10431
	CRES 303/304 BAR	10506
	CRES 300 SERIES WIRE	10514
	CRES 302 WIRE	10520
	CRES 310 BAR ANNEALED	10633
	CRES 440A BAR ANNEALED	30002
	CRES 430 BAR ANNEALED	30066
	CRES 303 BAR FREE MACHINE	30080

SPECIFICATION	DESIGNATION	MATCD
QQ-S-763	CRES 446 BAR	30094
	CRES 410 BAR ANNEALED	30114
	CRES 431 BAR ANNEALED	30120
	CRES 420 BAR	30136
	CRES 316 BAR CONDITION A	50059
	CRES 440A BAR QUENCHED AND TEMPERED	50064
	CRES 416 BAR COLD FINISHED	50065
	CRES 416 BAR QUENCHED & TEMPERED	50066
	CRES 302 ROD	50768
	CRES 302 SHAPES	50769
	CRES 302 FORGING	50770
	CRES 303 WIRE	50774
	CRES 304 FORGING ANNEALED	50775
	CRES 304 SHAPE CONDITION B	50779
	CRES 304 FORGING CONDITION B	50780
	CRES 304 WIRE CONDITION B	50781
	CRES 304L FORGING	50786
	CRES 304L TUBE	50787
	CRES 316L SHAPE ANNEALED	50803
	CRES 316L FORGING ANNEALED	50804
	CRES 316L WIRE ANNEALED	50805
	CRES 321 FORGING ANNEALED	50806
	CRES 321 TUBE ANNEALED	50807
	CRES 431 FORGING PANCAKE QUENCHED AND TE	50816
	CRES 440B BAR ANNEALED	50821
	CRES 440C BAR ANNEALED	50822
	CRES 440B BAR QUENCHED & TEMPERED	50823
	CRES 440C CASTINGS INVESTMENT QUENCHED &	50824
	CRES 430 SHAPES ANNEALED	52440
	CRES 347 BAR ANNEALED	52773
QQ-S-763/766	CRES 300 SERIES	10268
QQ-S-764	CRES 203EZ BAR FULL HARD	53128
QQ-S-766	CRES 301 SHEET ANNEALED 1/2 HARD 125KSI	10088
	CRES 304 PLATE ANNEALED	10090
	CRES 304L SHEET ANNEALED	10092
	CRES 310 SHEET ANNEALED	10094
	CRES 316L SHEET ANNEALED	10096
	CRES 347 SHEET ANNEALED	10099
	CRES 300 SERIES	10268
	CRES 302 PLATE ANNEALED THRU 1/2 HARD	10294
	CRES 301/302 SHEET ANNEALED	10350
	CRES 300 SERIES NON-FREE MACH	10431
	CRES 300 SERIES WIRE	10514
	CRES CUSTOM 455 H1000	10694
	CRES 302 STRIP 1/2 HARD	50365
	CRES 302 SHEET 1/2 HARD	50366
	CRES 304 SHEET ANNEALED THRU 1/2 HARD	50367
	CRES 301 STRIP ANNEALED 1/2 HARD 125 KSI	50763
	CRES 304 SHEET ANNEALED	50777
	CRES 304 STRIP ANNEALED	50778
	CRES 310 PLATE ANNEALED	50795
	CRES 310 STRIP ANNEALED	50796
	CRES 316 PLATE ANNEALED	50799
	CRES 316 STRIP ANNEALED	50800
	CRES 316L PLATE ANNEALED	50801

MSFC-HDBK-527 REV F ■ 9999942 0005074 8 ■

Information Handling Services, 2000

TABLE 1C

METALS BY CODE

Information Handling Services, 2000

DATE: 12/23/88
METALS BY MATERIAL CODE

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

MATCD	PAGE	DESIGNATION
10001		DELETED SEE 10389
10002		DELETED SEE 10387, 50727
10003		DELETED SEE 50223
10004	35	AL 2024-T8X BAR EXTRUDED
10005	33	AL 2024-T81 TUBE DRAWN SEAMLESS
10006	36	AL 2124-T851 PLATE
10007	42	AL 2219-T852 FORGING HAND
10009	177	INCONEL 600 WIRE ANNEALED
10010		DELETED SEE 10006
10011	168	CRES A286 BAR 140 KSI
10013	41	AL 2219-T8511 BAR EXTRUDED
10014	39	AL 2219-T6 FORGING HAND
10015	40	AL 2219-T62 SHEET
10016	65	AL 5083-H32 SHEET
10017	64	AL 5083-H111 BAR EXTRUDED
10018	82	AL 6061-T4 SHEET
10019	81	AL 6061-T4 BAR ROLLED
10020	84	AL 6061-T4511 BAR EXTRUDED
10021	82	AL 6061-T4 TUBE DRAWN SEAMLESS
10022	86	AL 6061-T6 SHEET
10023	85	AL 6061-T6 BAR ROLLED
10024	85	AL 6061-T6 BAR EXTRUDED
10025	86	AL 6061-T6 TUBE DRAWN SEAMLESS
10026	106	AL 7049-T73 FORGING
10028	111	AL 7075-T6 SHEET
10032	205	TITANIUM 6AL 4V FORGING HI-QUAL
10033	58	AL 5052-H191 FOIL
10034	205	TITANIUM 6AL 4V PLATE DIFFUSION BOND
10036	39	AL 2219-T62 BAR EXTRUDED
10037	149	CRES 17PH-4MO H1150M BAR EXTRUDED
10038	177	INCONEL 600 TUBE ANNEALED
10039	186	PLATING SILVER
10041	121	AL 7075-T76XXX EXTR EXFR RES
10043	119	AL 7075-T73XX SHEET
10044	121	AL 7075-T76X SHEET CLOSE TOLERANCE
10045		DELETED SEE 50280 , 50281
10046	186	PLATING NICKEL ELECTROLESS
10047	118	AL 7075-T7351 BAR ROLLED
10048	119	AL 7075-T7352 FORGING
10049		DELETED SEE 50282 50283
10050	53	AL 356.0-T51 CASTINGS PERMANENT MOLD
10051	52	AL 356.0-O CASTINGS SAND
10052	53	AL 356.0-T6 CASTINGS INVESTMENT
10053	128	AL A356.0-T61 CASTINGS
10054	206	TITANIUM COMM PURE SHEET ANNEALED 55KSI
10055	206	TITANIUM COMM PURE BAR ANNEALED 55KSI
10056	206	TITANIUM COMM PURE BAR 55KSI
10057	204	TITANIUM 5AL 2.5SN PLATE ANNEALED
10058	204	TITANIUM 5AL 2.5SN BAR FORGING ANNEALED
10059	204	TITANIUM 5AL 2.5SN BAR EXTRUDED ANNEALED
10060	204	TITANIUM 5AL 2.5SN BAR FORGING ANNEALED ELI
10061	203	TITANIUM 3AL 2.5V TUBE
10065	205	TITANIUM 6AL 4V SHEET ANNEALED
10066	204	TITANIUM 6AL 4V BAR HI-QUAL 55KSI
10067	204	TITANIUM 6AL 4V BAR ROD EXTRUDED ANNEALED
10068	205	TITANIUM 6AL 4V SHEET
10069	204	TITANIUM 6AL 4V BAR
10070	204	TITANIUM 6AL 4V BAR EXTRUDED STA
10072	206	TITANIUM 6AL 6V 2SN SHEET ANNEALED
10073	148	CRES 17PH-4MO H1025 FORGING
10074	148	CRES 17PH-4MO H1150 BAR
10075	149	CRES 17PH-4MO H1150M FORGING EXTRUSION VM
10076	149	CRES 17PH-4MO H1150M SHEET
10077	149	CRES 17PH-4MO H1150M CASTING
10078	146	CRES 15PH-5MO H1150M BAR
10079	189	SOLDER SN 50/60/62/63
10081	144	CRES 14PH-8MO H1050 SHEET
10083	161	CRES 316L BAR ANNEALED
10084	169	CRES AM-350 SCT1000 TUBE
10085	130	AM 355 SCT 1000 FORGING
10087	153	CRES 301 PLATE FULL HARD
10088	153	CRES 301 SHEET ANNEALED 1/2 HARD 125KSI
10089	154	CRES 302 BAR COLD DRAWN 100KSI
10090	156	CRES 304 PLATE ANNEALED
10091	156	CRES 304 BAR CONDITION B
10092	158	CRES 304L SHEET ANNEALED
10093	158	CRES 304L TUBE CONDITION A & B
10094	159	CRES 310 SHEET ANNEALED
10095	160	CRES 316 SHEET ANNEALED
10096	161	CRES 316L SHEET ANNEALED
10097	162	CRES 321 SHEET ANNEALED
10098	161	CRES 321 BAR ANNEALED
10099	162	CRES 347 SHEET ANNEALED
10100		DELETED SEE 52773
10101	162	CRES 321 TUBE ANNEALED SEAMLESS
10102	162	CRES 341 TUBE ANNEALED SEAMLESS
10103	153	CRES 21-6-9 SHEET ANNEALED
10104	152	CRES 21-6-9 BAR ANNEALED
10106	167	CRES 440C BAR QUENCHED AND TEMPERED
10107	193	STEEL 52100 BAR 180-200 KSI
10108	191	STEEL 4130 SHEET 120-180 KSI
10109	191	STEEL 4130 BAR 125-180 KSI
10110	192	STEEL 4330V BAR >200 KSI
10111	40	AL 2219-T81 SHEET
10112	59	AL 5052-H32 SHEET
10114	192	STEEL 4340 BAR 180-200 KSI
10115	60	AL 5052-H36 SHEET
10118	182	MAGNET NI-FE SHEET MUMETAL
10119	133	BRAZE 82AU 18NI
10121	75	AL 5456-H323 SHEET
10122	192	STEEL 4140 BAR <201 KSI
10123	183	MULTIPHASE MP35N
10124	168	CRES A286 SHEET 140KSI UTS
10125	168	CRES A286 FORGING 140KSI
10126	179	INCONEL 718 SHEET ST1900
10127	179	INCONEL 718 BAR ST1900F
10128	179	INCONEL 718 SHEET ST1750
10129	179	INCONEL 718 BAR ST1750F
10131	182	MAGNET NI-FE ALLOY BAR NI77 CU5 CR1.5
10132	185	NICKEL U-500 ST BAR

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
10134	177	INCONEL 600 SHEET ANNEALED
10135	177	INCONEL 600 BAR ANNEALED
10136	180	INCONEL X750 STRIP EXTRUDED
10138	180	INCONEL X750 SHEET STA
10139	180	INCONEL X750 BAR STA
10140	178	INCONEL 601 SHEET ANNEALED
10141	178	INCONEL 625 STRIP ANNEALED
10142	174	HAYNES 188 FOIL ANNEALED
10143	174	HAYNES 188 TUBE ANNEALED
10144	174	HAYNES 25 SHEET ANNEALED
10145	174	HAYNES 25 BAR ANNEALED
10146	173	ELGILOY RC55 WIRE SPRING
10147	150	CRES 17PH-7MO CH900 WIRE
10148	154	CRES 302 SPRING CONDITION B WIRE
10149	131	BE-CU #175 WIRE CONDITION A
10150	210	WIRE ALLOY X750 SPRING TEMPER
10153	191	STEEL 4140 150KSI CASTING INVESTMENT
10154	192	STEEL 4340 180KSI CASTING INVESTMENT
10155	157	CRES 304L CASTING INVESTMENT
10156	147	CRES 17PH-4MO 150KSI CASTING INVESTMENT
10157	162	CRES 347 CASTING INVESTMENT ANNEALED
10158	174	HASTELLOY C CASTING INVESTMENT ANNEALED
10159	160	CRES 316 CASTING INVESTMENT ANNEALED
10162	207	WELD WIRE AL 5356 UNCOATED
10163	207	WELD WIRE AL 5556 UNCOATED
10164	209	WELD WIRE TI CP UNCOATED
10165	207	WELD WIRE 5AL 2.5SN UNCOATED
10166	209	WELD WIRE TI 6AL 4V ELI BAR
10167	208	WELD WIRE ELI TI CP UNCOATED
10168	208	WELD WIRE ELI TI 5AL 2.5SN
10169	208	WELD WIRE ELI TI 6AL 4V
10170	207	WELD WIRE CRES 17-4PH
10171	57	AL 5052 TUBE
10172	207	WELD WIRE CRES 14PH-8
10173	207	WELD WIRE CRES 13PH-8
10174	208	WELD WIRE CRES AM350 UNCOATED
10175	208	WELD WIRE CRES 308 ELEC
10176	208	WELD WIRE CRES 347
10177	208	WELD WIRE CRES 310 UNCOATED
10178	208	WELD WIRE CRES 316 UNCOATED
10179	208	WELD WIRE CRES 316 ELC
10180	208	WELD WIRE CRES 321 UNCOATED
10181	207	WELD WIRE CRES 21-6-9
10182	209	WELD WIRE STEEL ER 502
10183	209	WELD WIRE STEEL OXWELD 71
10184	209	WELD WIRE STEEL 17-22AS
10185	207	WELD WIRE AL 4043 UNCOATED
10186	209	WELD WIRE STEEL 9NI 4CO 2C
10187	209	WELD WIRE STEEL 18-7 MAR
10188	208	WELD WIRE NI BASE HASTELLOY W
10189	209	WELD WIRE NI BASE INCO 718
10190	209	WELD WIRE NI BASE INCO 62
10191	209	WELD WIRE NI BASE INCO 69
10192	209	WELD WIRE NI BASE INCO 82
10193	209	WELD WIRE NI BASE INCO 625
10194	207	WELD WIRE CO BASE HAYNES 188
10195	207	WELD WIRE CO BASE HAYNES 25
10196	133	BRAZE 81.5AU 16.5CU 2.0NI
10197	132	BRAZE 52.5CU 38.5MN 9NI
10198	133	BRAZE 72AU 22NI 6CR
10199	134	BRAZE LTC 80/20 NI MATRIX
10200	132	BRAZE 62.5AG 32.5CU 5NI
10201	197	STEEL 9NI 4CO (.20C) SHEET 180-200 KSI
10202	197	STEEL 9NI 4CO (.20C) BAR 190 KSI
10203	75	AL 5456-H112 SHEET
10204	75	AL 5456-H343 SHEET
10205	35	AL 2024-T8X SHEET
10206	189	SOLDER SN 40 WRAP 4
10207	130	AM 350 SCT 850 SHEET
10209	178	INCONEL 706 SHEET
10210	31	AL 2024-T62 SHEET
10213	137	COPPER 100% SHEET ANNEALED
10215	182	MAGNET NI-FE ALLOY SHEET
10216	32	AL 2024-T62 TUBE
10217	4	AL 1100 BAR
10218	79	AL 6061 BAR
10219	160	CRES 316 WIRE CONDITION A & B
10220	157	CRES 304 WIRE ANNEALED
10222	183	MONEL 400 67NI 30CU WIRE ANNEALED
10223	210	WIRE CU,NI COATED ELECTRICAL
10224	35	AL 2117-H13 ROD
10225	184	NICKEL 200 SHEET LOW CARBON
10226		DELETED SEE 10101
10227	162	CRES 347 TUBE ANNEALED
10228	208	WELD WIRE CRES AM355 UNCOATED
10229	207	WELD WIRE CRES 13-7 MO ELEC
10230	208	WELD WIRE CRES A286 UNCOATED
10231	210	WIRE ALLOY X750 #1 TEMPER
10232	203	STEEL WIRE SPRING MUSIC
10233	157	CRES 304L BAR ANNEALED
10234	131	BRASS SHIM STOCK >1/8HD COMP 2
10235	181	MAGNET HI-PERM MUMETAL
10237	201	STEEL SHIM STOCK COMP 4 MILD
10238	126	AL 7178-T76XX SHEET CLOSE TOLERANCE
10242	132	BRAZE 60AG 30CU 10SN
10243	132	BRAZE 63AG 28.5CU 6SN 2.5NI
10244	133	BRAZE AG15 80CU 5P
10245	133	BRAZE 73NI 4.5SI 14CR 3.1B4.5
10246	133	BRAZE 92NI 4.5SI 3.1B
10247	134	BRAZE ELEC COPPER UNINSULATED
10248	134	BRAZE COPPER FLAT RODS
10250	181	MAGNET 50NI 50FE BAR
10252	129	AL SHIM STOCK (COMP 1)
10253	74	AL 5456-H111 BAR EXTRUDED
10254	75	AL 5456-H112 BAR EXTRUDED
10255	75	AL 5456-H321 SHEET
10256	130	BE-CU #172 WIRE CONDITION A
10257	129	AL BRONZE #630 ROD 110 KSI
10258	129	AL BRONZE #630 CASTINGS BEARING 95 KSI
10260	32	AL 2024-T81 FOIL

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005077 3 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
10261	64	AL 5056-H39 FOIL
10262	154	CRES 302 SHEET
10263	157	CRES 304 SHEET HARD
10264	147	CRES 15PH-7MO SHEET
10267	168	CRES A286 FASTENER MATERIAL SH
10268	153	CRES 300 SERIES
10269	181	MAGNET ARMCO INGOT IRON
10270	181	MAGNET ALNICO V. VI. VIII
10271	130	BE-CU #173 BAR
10273	42	AL 2419-T8XX SHEET
10274	186	PLATING NIICKEL TIN ELECTROLESS
10275	186	PLATING CHROMIUM CLASS 2
10276	136	COATING ANODIC
10277	137	COATING ANODIC T2
10279	8	AL 1100-O SHEET
10280	178	INCONEL 706 BAR STA
10281	186	PLATING SILVER FASTENERS ONLY
10282	48	AL 3003-O SHEET
10283	137	COATING ANODIC T3 HARD
10284	193	STEEL 4620 BAR 165KSI
10285	142	CRES 13PH-8MO H1050 BAR
10286	180	INCONEL 718 TUBE ST1950F
10287	180	INCONEL 718 TUBE
10288	178	INCONEL 625 BAR ANNEALED
10289		DELETED SEE 10099, 10097
10290		DELETED SEE 10280, 50879, 50880
10291	32	AL 2024-T6X BAR EXTRUDED
10292	31	AL 2024-T6 ROD ROLLED
10293	53	AL 357.0-F CASTINGS PERMANENT MOLD
10294	154	CRES 302 PLATE ANNEALED THRU 1/2 HARD
10295	205	TITANIUM 6AL 6V 2SN BAR ANNEALED
10296	160	CRES 316 SPRING WIRE CONDITION B
10297	174	HAYNES 188 BAR ANNEALED
10298	206	TITANIUM COMM PURE TUBE ANNEALED <55KSI
10299	190	STEEL 1095 CONDITION 2 <200KSI SPRING
10300	191	STEEL 4130 TUBE 125-180 KSI
10301		DELETED SEE 50070
10304		DELETED SEE 10171, 10500
10305		DELETED SEE 10123
10306	158	CRES 304L ROD ANNEALED
10308	186	PLATING NICKEL ELECTRODEPOSIT
10309	104	AL 6951 SHEET CLAD W/AL 4045
10310	203	TITANIUM 3AL 2.5V FOIL ANNEALED
10311	186	PLATING COPPER ELECTRODEPOSIT
10312	186	PLATING TIN
10314	181	INVAR 36 BAR (GLASS SEALING)
10315	155	CRES 302/304/316 FASTENRS ONLY
10317	139	COPPER BAR BUS TYPE 1
10318	158	CRES 304L WIRE SCREEN
10320	184	NICKEL 99% ELECTROFORMED PARTS
10321	131	BRASS,ALL FORM
10322	135	BRONZE PHOSPHOR-ALL FORMS
10323	208	WELD WIRE CRES 349
10325	79	AL 6061 SHEET ANNEALED
10326	133	BRAZE 66NI 12MN 7SI 5CU (AMBRY930
10327	181	INDIUM (99.94%)
10328	186	PLATING GOLD
10329	128	AL BRONZE #606 FORGING 70 KSI
10330	210	WIRE COPPER TIN PLATED
10331	179	INCONEL 718 SHEET CEVM STA1900F
10332	179	INCONEL 718 BAR CEVM
10333	138	COPPER BAR ANNEALED HARD TEMPER
10334	155	CRES 302/304 FASTENER ONLY
10335	36	AL 2117-T4 ROD
10336	158	CRES 305 BAR ANNEALED
10337	89	AL 6061-T652 FORGING
10338	188	SOLDER 1.5% SILVER
10339	133	BRAZE 92.5 AG 7.2 CU .22 LI
10340	8	AL 1100-O TUBE
10341	192	STEEL 4340 BAR > 200KSI
10342	148	CRES 17PH-4MO H1025 SHEET
10343	141	CRES 13PH-8MO H1025 BAR
10344	142	CRES 13PH-8MO H1100 BAR
10346	138	COPPER ALLOY 110 SHEET
10348	9	AL 11XX FOIL ANNEALED
10349	155	CRES 302/304 1/4 HARD
10350	154	CRES 301/302 SHEET ANNEALED
10351	156	CRES 304 BAR ANNEALED
10352	140	COPPER WIRE AU PLATE ELECTRO DEPOSITED
10353	139	COPPER TUBE ANNEALED NI PLATED SPLICE
10354	138	COPPER ALLOY 102 WIRE
10356		DELETED SEE 30063
10357	209	WELD WIRE STEEL AWS E 705-2
10358	189	STEEL 1010 <180KSI
10359	189	STEEL 1010 TO 1040
10360	135	BRONZE PHOSPHOR SAE 660
10361	148	CRES 17PH-4MO H1100 CASTING INVESTMENT
10363	184	NICKEL BAR (ELECTRONIC)
10364	132	BRAZE 45 AG 15 CU 16 ZN 24 CD
10365	204	TITANIUM 6AL 4V BAR 120 KSI
10366	4	AL 1100 SHEET ANNEALED
10369	205	TITANIUM 6AL 4V FORGING ANNEALED
10370	160	CRES 316 BAR CONDITION A
10372	137	COPPER 62CU CDA350 BRASS COPPER
10373	187	RENE 41 BAR
10374	174	HASTELLOY X SHEET
10375	156	CRES 304 PLATE ANNEALED THRU 1/2 HARD
10376	128	AL BRONZE #623 BAR
10377	63	AL 5056 WIRE SCREEN
10378	147	CRES 17PH-4MO H1025 CASTING INVESTMENT
10380	161	CRES 321 FOIL
10381		DELETED SEE 10092, 10096, 10097, 10099
10382	154	CRES 302 BAR
10383	205	TITANIUM 6AL 4V FORGING STOCK
10385	48	AL 3003-O ROD EXTRUDED
10386	146	CRES 15PH-5MO H1150M FORGING
10387	146	CRES 15PH-5MO H1150 BAR
10388	146	CRES 15PH-5MO H1075 BAR
10389	145	CRES 15PH-5MO H1025 BAR
10390		DELETED SEE 10098, 50808, 50810, 52714, 52773

MSFC-HDBK-527 REV F ■ 9999942 0005078 5 ■

MATCD	PAGE	DESIGNATION
10391	155	CRES 302 WIRE SPRING TEMPER B
10392	168	CRES A286 SHAPE
10394	91	AL 6063-T42 BAR EXTRUDED
10395	129	AL C355.0-T6 CASTING
10396	128	AL A380 CASTINGS DIE
10397	174	HAYNES 188 SHEET ANNEALED
10398	204	TITANIUM 6AL 4V BAR DIFFUSION BOND
10399	147	CRES 17PH-4MO H1025 BAR
10400	180	INCONEL X750 STRIP STA
10401	204	TITANIUM 6AL 4V BAR STA
10402	204	TITANIUM 6AL 4V BAR ANNEALED STA
10403	178	INCONEL 625 TUBE ANNEALED
10404	178	INCONEL 625 SHEET ANNEALED
10405		DELETED SEE 10126, 50882, 50883
10406	179	INCONEL 718 BAR
10407		DELETED SEE 10126, 50882, 50883
10408	24	AL 2024-O PLATE CLAD
10409	150	CRES 17PH-7MO CH900 SHEET
10410	129	AL BRONZE #637
10411	31	AL 2024-T6 FORGING
10412	40	AL 2219-T62 TUBE
10413	157	CRES 304 TUBE/PTFE ANNEALED
10414	205	TITANIUM 6AL 6V 2SN EXTRUSION
10417	189	SPRING ALLOY COMP 2 TYPE1 WIRE
10418	134	BRONZE 60.5CU 3MN BAL ZN ROD
10419	151	CRES 18-9 WIRE SPRING TEMPER
10420	34	AL 2024-T8510 BAR EXTRUDED
10421	118	AL 7075-T73511 BAR EXTRUDED
10423	154	CRES 302 BAR COLD DRAWN 125KSI
10425	148	CRES 17PH-4MO H1025 EXTRUSIONS
10426		DELETED SEE 10099
10427	148	CRES 17PH-4MO H1150 BAR EXTRUDED
10428		DELETED SEE 10147
10429	132	BRAZE 65AG 20CU 15ZN
10430	148	CRES 17PH-4MO H1075 FORGING
10431	153	CRES 300 SERIES NON-FREE MACH
10432	156	CRES 304 1/4 HARD FOIL COLD ROLL
10433	187	SILVER
10434	133	BRAZE AL ALLOY 4145 WIRE
10435	149	CRES 17PH-4MO H1150M BAR
10436	157	CRES 304 TUBE 1/8 HARD
10437	48	AL 3003-O TUBE EXTRUDED
10438	204	TITANIUM 6AL 4V BAR ANNEALED 125KSI ELI
10439	139	COPPER WIRE (RIVETS)
10440	133	BRAZE AL ALLOY 4047
10441	184	NICKEL ALLOY 902 SPAN-C
10442	182	MAGNET NI-FE ALLOY ROD
10443	64	AL 5056-O ROD ROLLED
10444	206	TITANIUM COMM PURE BAR ANNEALED 70 KSI
10446	187	RENE 41 SHEET
10448	188	SOLDER 96SN
10449	188	SOLDER 5SB
10450	180	INCONEL X750 SHEET ANNEALED
10451	151	CRES 17PH-7MO SHEET CONDITION C
10452	179	INCONEL 718 CASTING ST1900
10453	203	TITANIUM 3AL 2.5V TUBE ANNEALED
10454	108	AL 7075 FORGING HAND
10455	163	CRES 347 WIRE CONDITION A & B
10456	167	CRES A286 BAR 130-140KSI UTS
10457	111	AL 7075-T6 SHEET CLAD
10458	132	BRAZE 56AG 22CU 17ZN 5SN
10459	132	BRAZE 40AG 30CU 28ZN 2NI
10460	134	BRAZE BNI-6 11NI .015C
10461	133	BRAZE 75AG 25ZN
10462	132	BRAZE 20AG 45CU 35ZN ALLOY 202
10463	132	BRAZE 55AU 25AG 15PD 5PT
10464	173	CRES NITRONIC 60
10466	39	AL 2219-T42 RIVETS
10467	131	BE-CU CASTING
10468	203	STOODY NO. 2 >200KSI
10469	139	COPPER WIRE AG PLATE SOFT OR ANN
10470	199	STEEL CARBON BEARING <200KSI
10471	148	CRES 17PH-4MO H1100 BAR
10472	136	COATING AL PLASMA
10473	181	MAGNET 79NI 4MO 17FE PERMALLOY
10474	160	CRES 316 TUBE SEAMLESS
10475	158	CRES 305 SHEET
10476	148	CRES 17PH-4MO H1050 BAR
10477	184	NICKEL ALLOY 42 (GLASS SEALING)
10478	133	BRAZE 70AU 8PD 22NI
10479	133	BRAZE 82NI 4.5SI 7CR 3FE 3.1B
10480	134	BRAZE EASY-FLO 45
10481	132	BRAZE 50CO 8SI 19CR 17NI 4W.8B
10482		DELETED SEE 51332
10483	139	COPPER TUBE SEAMLESS
10484	173	CUPRON 45% NI 55% CU
10485	127	AL A356.0-T51 CASTING
10486		DELETED SEE 10301, 10122, 10511
10487	146	CRES 15PH-5MO H1150 TUBE
10488	184	NI80 20FE CO-NETIC AA ALLOY
10489	147	CRES 17PH-4MO H1000 CASTING SAND
10490	200	STEEL ELEC M19 (3SI)
10491	188	SOLDER 70SN 30PB
10492	194	STEEL 6150 50C 1CR 25V
10493	133	BRAZE AG-PLATIUM
10494	185	PALLADIUM 25% SILVER ALLOY
10495	184	NICKEL ALLOY 52 (GLASS SEALING)
10496	203	TIN
10497	201	STEEL SHEET PB-SN SOLDER <180 KSI
10499	203	STEEL WIRE COPPER/CLAD <180KSI
10500	62	AL 5052-O TUBE
10501	139	COPPER RODS
10503		DELETED SEE 10112, 50607
10505	179	INCONEL 718 FORGING ST1775F
10506	155	CRES 303/304 BAR
10507	100	AL 6262 BAR
10508	33	AL 2024-T851 BAR ROLLED
10509		DELETED SEE 10093 10105
10510		DELETED SEE 10093, 10101, 10226, 10102, 10227
10511	194	STEEL 8620 BAR

MSFC-HDBK-527 REV F 9999942 0005079 7

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
10512	155	CRES 303/305 BAR
10513	193	STEEL 4XXX <200 KSI
10514	153	CRES 300 SERIES WIRE
10515	200	STEEL HIGH CARBON >200 KSI
10516	151	CRES 17PH-7MO WIRE CONDITION C
10517	53	AL 356.0-T6 CASTINGS
10518	167	CRES A286 BAR 130-190KSI
10519	57	AL 5052 BAR
10520	155	CRES 302 WIRE
10521	18	AL 2014-T6 SHEET CLAD
10522	207	VELCRO (304/INCO-750/ELGILOY)
10523	134	BRAZE NEYORO AU-AG ALLOYS
10524	184	NICHROME 80NI-20CR
10525	24	AL 2024-O ROD ROLLED
10526		DELETED SEE NON-METALS
10527		DELETED SEE NON-METALS
10601	154	CRES 302 CASTING INVESTMENT
10602	135	BRONZE,TELNIC (99.9% CU)
10603		DELETED SEE 52912,52919,52910
10604	134	BRAZE PERMABRAZE 615
10605		DELETED SEE 10485
10606	151	CRES 18-8 SHIM STOCK
10607	137	COPPER 30NI ALLOY NO 715
10608	185	PALINEY #7 COMP D
10609	209	WIRE 479 92PT8W RESISTANCE
10610		DELETED SEE 50074 50128
10611		DELETED SEE 10484
10612	1	65CU-18NI-17ZNALLOY NO 752
10613	128	AL A360-F CASTINGS DIE
10614	137	COPPER 6%NI
10615	137	COPPER 22NI
10616	188	SOLDER 28SN 44PB 28BI
10617	194	STEEL 6150 BAR >200 KSI
10618	185	PERMENDUR 49CO 2V 49FE
10619	135	BRONZE OILITE 10SN
10620	138	COPPER 97.8 1PB 1NI .2P
10621	139	COPPER PD-135 99.2CU .4CD .4CR
10622	158	CRES 305 WIRE
10623	137	COPPER 3NI WIRE
10624	132	BRAZE 54AG 40CU 5ZN 1NI
10625		DELETED SEE 53079
10626	188	SOLDER SN 10
10627	188	SOLDER ALPHA 111 PB-SN-18CD
10628	185	PALLADIUM BLACK 99.95%PD
10629	187	PLATINUM BLACK (PT POWDER)
10630	181	LEDLOY-A STEEL (180-200KSI)
10632	173	GOLD-PLATINUM ALLOY B-12% PT
10633	158	CRES 310 BAR ANNEALED
10634	138	COPPER ANACONDA # 1870
10635		DELETED SEE 10351
10636	53	AL 380 CASTINGS
10637	184	NICKEL ALLOY 20CR3AL2CO75NI
10638	131	BE-CU #175
10639	52	AL 355.0 CASTING
10640	136	COATING ANODIC T1
10641	54	AL 43 CASTING INGOT
10642	140	COPPER WIRE NI ELECTRICAL CLAD
10643	143	CRES 13PH-8MO H1150
10644		DELETED SEE 10484
10645	157	CRES 304 SPRING WIRE FULL HARD
10646	174	HAYNES STELLITE 6B
10647	183	MARAGING STEEL 250>200KSI
10648	189	STEEL 1008-1020 <180 KSI
10649	137	COATING ANODIC TIODIZE
10650	132	BRAZE 56AG 42CU 2NI
10651	134	BRAZE WILBRAZE 6022
10652		DELETED SEE 10477
10653	189	STEEL 0.90-1.30 CARBON BAR <180
10654	188	SOLDER 5.5AG
10655	207	WELD WIRE CRES 29-9
10656	135	BRONZE CASTING CA 922
10657	134	BRAZE LITHOBRAZE
10658	210	WIRE NICHROME V COATING ALLOY
10659	43	AL 3003 1-SIDE CLAD W/AL 4343
10660	135	CB 103 BAR ANNEALED
10661	173	CRES XM-27 E-BRITE Z6-1 BAR
10662	210	WIRE 88CU 12NI
10663	210	WIRE 75NI 20CR RESIST EVANOPHM
10664	129	AL CASTING 99.75% ALUMINUM
10665	203	T/C ALLOY PLATINUM/PT-RH
10666	203	T/C ALLOY CHROMEL-ALUMEL WIRE
10667	188	SOLDER 95SN 5AG
10668	203	T/C ALLOY PLATINUM TY RN WIRE
10669		DELETED SEE 10458
10670	79	AL 6061 BAR ANNEALED
10671	162	CRES 347 RIVET CONDITION A
10672	54	AL 4343 METAL BRAZING FILLER
10673	134	BRAZE BNI-4 94NI 3.5SI 1.8B
10674	156	CRES 304 CASTING INVESTMENT ANNEALED
10675	151	CRES 18-8 (303) WIRE
10677	210	WIRE NICHROME-TOPHET C RESIST
10678	210	WIRE COPPER STEEL CLAD
10679	203	STOODY NO. 6
10680	210	WIRE 60NI-16CR-24FE ELECTRICAL
10681		DELETED SEE 50224 OR 50225
10682	203	T/C ALLOY 50% RHENIUM
10683	188	SOLDER SN 20
10684	9	AL 1175-O CASTING SAND,MOLD,DIE
10685	137	COPPER 55 18NI 27ZN ALLOY 770
10686		DELETED SEE 50231
10687	201	STEEL SHEET LOW CARBON 180-200 KSI
10688	148	CRES 17PH-4MO H1075 TUBE
10689	181	MAGNET 17CO-83FE ALLOY
10690	188	SOLDER 5SN 95PB
10691	203	TANTALUM
10692	203	T/C ALLOY W-5 RHEN/W-26 RHEN
10693	148	CRES 17PH-4MO H1075 BAR
10694	171	CRES CUSTOM 455 H1000
10695	180	INCONEL X750 WIRE SPRING STA
10696	202	STEEL T-I 13V 11CR 3AL SPRING WIRE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005080 3

MATCD	PAGE	DESIGNATION
10697	181	MAGNET ALLEGHENY LUDLUM
10698	139	COPPER SILICON-BRONZE ALLOY # 655
10699	202	STEEL TOOL CARBON VANAD <200KSI
10700	208	WELD WIRE NI + CO
10701		DELETED SEE 10685 & 10715
10702	152	CRES 19-9DL SHEET ANNEALED
10703	187	PLATINUM-COBALT ALLOY
10704	188	SOLDER 80AU 20SN
10705	133	BRAZE 99.9 AU
10706		DELETED SEE 10193
10707	136	CO BASE 32CR 18W 2.6C STAR J PM
10708	38	AL 2219-T351 SHEET
10709	131	BERYLLIUM BAR
10710	132	BRAZE 50AG 15CU 16ZN 20CD
10711	188	SOLDER INDALOY # 2
10712	203	TITANIUM 45%CB BAR ANNEALED
10713	185	PALINEY 6 PD-PT-AG-CU ALLOY
10714	134	BRAZE NEYORO AU-PT-AG-CU ALLOY
10715	137	COPPER 65 18NI 17ZN ALLOY 752
10716	131	BE-CU #175 BAR
10717	137	COATING PLASMA SPRAY DEPOSITED
10718	171	CRES DISCALOY
10719	136	CB C-103 BAR INGOT
10720	199	STEEL CARBON RC 29-33
10721	133	BRAZE AL ALLOY 10SI 1.2MN
10722	182	MAGNET VICALLOY 10V52CO38FE
10723	181	IRIDIUM
10724	136	CB-1ZR
10725	203	T/C ALLOY COPPER TY RN
10726	190	STEEL 17-22A BAR FORGING TUBE
10727	178	INCONEL 625 BAR
10728	132	BRAZE 50AG 16CU 15ZN 3NI
10729	205	TITANIUM 6AL 4V CASTING INVESTMENT 180-200KSI
10730	209	WELD WIRE STEEL E10018
10731	190	STEEL 1340 (180-200 KSI)
10732	82	AL 6061-T4 TUBE
10733	210	WIRE CU AG COATED CLAD
10734	199	STEEL 9NI 4CO BAR
10735		DELETED SEE 10607
10736	97	AL 6101 FORMS EXTRUDED METAL
10737	193	STEEL 50100 BAR 180-200 KSI
10738	130	AM 350 SCT 1000 SHEET
10739	209	WELD WIRE TI 6AL 4V
10740	183	MONEL K-500 ALLOY
10741	131	BERYLCO 440
10742	184	NI-AL-FE-CU ALLOY
10743	136	COATING ANODIC DOW 17
10744	23	AL 2024-O BAR ROLLED
10745	177	INCONEL 100 CASTING INVESTMENT
10746	187	RA 330 NI-CR-FE-SI ALLOY
10747	183	MERCURY
10748	182	MANGANIN 87CU-13MN
10749	181	IRON-MALLEABLE
10750	33	AL 2024-T81 SHEET
10751	147	CRES 15PH-5MO SHEET
10752	102	AL 6262-T9
10753	199	STEEL CARBON MOLYBDENUM 180-200KSI
30002	166	CRES 440A BAR ANNEALED
30008	166	CRES 440C BAR COLD FINISHED
30014		DELETED SEE 10264,50730
30020	151	CRES 17PH-7MO TH1100 SHEET
30029	107	AL 7050-T7351 SHEET & PLATE
30038	202	STEEL TOOL M50 RC58-64 BAR
30039	202	STEEL TOOL M2 RC 32-48 BARS
30040	202	STEEL TOOL D2 RC 58-62 BARS
30044	130	BE 2% BEO SHEET
30047	195	STEEL 9254 SPRING Q&T
30050	206	TUNGSTEN SUPERDENSALLOY 180
30051	136	CB 752 SHEET ANNEALED
30052	136	CB C129Y SHEET ANNEALED
30053	136	CB FS 85 SHEET
30055	26	AL 2024-T351 SHEET
30063	185	NITRALLOY 135MOD QUENCHED AND TEMPERED BAR
30064	190	STEEL 1213 COLD FINISH <180KSI
30065	190	STEEL 1215 COLD FINISH <180KSI
30066	164	CRES 430 BAR ANNEALED
30067		DELETED SEE 10365
30069	184	NICKEL ALLOY 53 (GLASS SEALING)
30071	29	AL 2024-T4/T3511
30073	196	STEEL 9310 HOT ROLLED BAR
30074	194	STEEL 8620 BAR CAS-HD >200 KSI
30075	164	CRES 416 BAR ANNEALED
30076	200	STEEL ELEC 1.0SI CORE FE CST
30077	150	CRES 17PH-7MO RH900 SHEET
30079	194	STEEL 6150 (RC 46-50)
30080	155	CRES 303 BAR FREE MACHINE
30082	186	PLATING CADMIUM ELECTRODEPOSIT
30083	173	HASTELLOY B BAR
30084	174	HAYNES STELLITE 31 INVESTMENT CAST
30085	187	RENE 95 BAR
30086	192	STEEL 4140 BAR DIE DRAWN 180 KSI
30087	194	STEEL 8735 SHEET >200 KSI
30088	197	STEEL 9NI 4CO (.30C) BAR 180-200 KSI
30089	199	STEEL CARPENTER 158 CARB <200 KSI
30090	171	CRES GREEK ASCOLOY BAR QUENCHED & TEMPERED
30091	151	CRES 17PH-7MO TH1050 BAR
30092	200	STEEL H-11 BAR >200 KSI
30093	167	CRES 446 PLATE
30094	167	CRES 446 BAR
30095	174	HAYNES STELLITE 21 INVESTMENT CAST
30096	195	STEEL 8740 BAR >200 KSI
30097	131	BORON/AL 6061 TUBE ANNEALED
30098	202	STEEL TOOL 01 RC24-27
30099	21	AL 2017-O BAR ROLLED
30100	183	MOLYBDENUM
30101		DELETED SEE NON-METALS
30102	200	STEEL ELEC A-FM SI CORE IRON
30103		DELETED SEE NON-METALS
30104	190	STEEL 200-220 KSI
30106	41	AL 2219-T852 FORGING

MSFC-HDBK-527 REV F ■ 9999942 0005081 5 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
30107	206	TUNGSTEN MALLORY ALLOY 2000
30108	25	AL 2024-T3 FASTENERS ONLY
30109	200	STEEL D6AC BAR TUBE,FORGING,CVEM 180KSI
30110	200	STEEL D6AC SHEET PLATE >180 KSI
30111	25	AL 2024-T3 SHEET
30112	25	AL 2024-T3 BAR EXTRUDED
30113	141	CRES 13PH-8MO H1000 BAR
30114	163	CRES 410 BAR ANNEALED
30115	187	PLATINUM & PLATINUM ALLOY
30116	180	INCONEL 903 SHEET,PLATE,STRIP
30117		DELETED SEE 52620 - 52626
30118	181	K-6 ALLOY PLATING NI PB CR
30119	137	COATING ANODIZING, BERYLLIUM
30120	165	CRES 431 BAR ANNEALED
30121	151	CRES 17PH-7MO SHEET CONDITION A
30122	112	AL 7075-T62 BAR EXTRUDED
30123		DELETED SEE 30159,30098
30125	207	WASPALOY BAR FORGING
30126	171	CRES CUSTOM 455 H950
30127	173	GOLD ALLOY 60AU 35AG 5PT TUBE
30128	186	PLATING RHODIUM ELECTRODEPOSIT
30129	136	CB ROD
30130	201	STEEL LOW ALLOY 17-22A
30131	130	BE BRAKEGRADE ES13.3.19
30132	188	SOLDER 34SN 63PB 3ZN
30133	194	STEEL 8630 BAR >200 KSI
30135	10	AL 2011-T6 BAR
30136	164	CRES 420 BAR
30138	182	MAGNET SM CO (MC203-0002)
30139	193	STEEL 4XXX CASTING INVESTMENT >200 KSI
30140	24	AL 2024-O SHEET
30141	181	LEAD ALLOY 6.5SB .5SN CASTING
30142	190	STEEL 1095 (SPRING)
30143	187	PLATING ZINC
30144	203	TITANIUM 13V-11CR-3A1
30145	184	NICKEL 30CR 3AL 3FE
30146	187	SILVER 18% NICKEL ALLOY
30148	186	PLATING CADMIUM/TITANIUM
30149		DELETED SEE 30114,50129,50814
30150		DELETED SEE 52780 - 52784
30151	206	TUNGSTEN KENNERTIUM W-2
30152	201	STEEL SINTERE D LOW ALLOY 180-200 KSI
30153	173	GOLD-PT ALLOY
30154	181	MAGNESIUM ALLOY PHOTO GRADE
30155		DELETED SEE 10195
30156	188	SOLDER EUTEC 157
30157	182	MAGNET SUPERPERM 80NI4MO16FE
30158	123	AL 7178-T6 SHEET CLAD
30159	149	CRES 17PH-4MO H900 BAR
30160	146	CRES 15PH-5MO H900 BAR
30161	182	MARAGING 18% STEEL >200KSI
30162	183	MARAGING VASCO MAX 300 STEEL
30163	135	CB 103 SHEET
30165	192	STEEL 4330V QUENCHED & TEMPERED 180-200
30166		DELETED SEE 10453

MATCD	PAGE	DESIGNATION
30168	188	SOLDER CERTANIUM 36EC
30169		DELETED SEE 50301 , 50302 ,50303 50304
30171	188	SOLDER 51SN 30PB 18CD
30185	134	BRAZE AL#22-O SHEET 2-SIDES CLAD
30186	134	BRAZE AL#21-O SHEET (CL ONE SIDE
30187	187	SILICON
30188	77	AL 5652-O SHEET
30189		DELETED SEE 10507, 50660, 50661
30190	186	PLATING NICKEL-CHROMIUM
30191	186	PLATING NICKEL-GOLD
30192	210	WIRE COPPER-NICKEL-MANGANESE
30193		DELETED SEE NON-METALS
30194	137	COATING FERRIC FEO.FE203
30195	130	AMERICIUM-241
30196		DELETED SEE NON-METALS
30197		DELETED SEE NON-METALS
30198		DELETED SEE NON-METALS
50053		DELETED SEE 50916
50054	193	STEEL 4344 SHEET ANNEALED
50055		DELETED SEE 10210
50057		DELETED SEE 10104,50759 - 50761
50058		DELETED SEE 10474
50059	160	CRES 316 BAR CONDITION A
50060	128	AL A356.0-T6 CASTING INVESTMENT
50062	200	STEEL D6AC 180KSI
50064	166	CRES 440A BAR QUENCHED AND TEMPERED
50065	164	CRES 416 BAR COLD FINISHED
50066.	164	CRES 416 BAR QUENCHED & TEMPERED
50067	201	STEEL M36 1.5%SI <180KSI
50068	140	COPPER WIRE FABRIC STEEL WELDED
50069	167	CRES A286 95KSI YIELD
50070	192	STEEL 4340 BAR ANNEALED
50071	158	CRES 304L WIRE
50072	39	AL 2219-T37 SHEET
50073	39	AL 2219-T352 FORGING
50074	207	WELD WIRE AL 2319
50076	38	AL 2219-T351 PLATE
50078	63	AL 5056 HONEYCOMB CORE
50079	38	AL 2219-T31 SHEET
50080	39	AL 2219-T42 SHEET
50081	42	AL 2219-T87 SHEET
50082	41	AL 2219-T851 PLATE
50083	200	STEEL D6AC FORGING >180 KSI
50084	168	CRES A286 BAR 180KSI
50085	156	CRES 304 PLATE
50086		DELETED SEE 10675
50088	38	AL 2219-T3511 BAR EXTRUDED
50089	120	AL 7075-T762 SHEET CLAD
50090	120	AL 7075-T7651 SHEET CLAD
50091	120	AL 7075-T76 SHEET CLAD
50092	32	AL 2024-T81 PLATE CLAD
50093	157	CRES 304 WIRE FABRIC
50094	72	AL 535-O CASTINGS SAND
50097	166	CRES 440 SHEET
50098	149	CRES 17PH-4MO H950 BAR

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005082 7

MATCD	PAGE	DESIGNATION
50099	173	GOLD WIRE (ELECTRICAL)
50100		DELETED SEE 50095
50101	110	AL 7075-T6 FORGING
50103	135	BRONZE MESH 40-50 MICRONS-FILTER
50104		DELETED SEE 10515
50105	132	BRAZE 50AG 15.5CU 15.5ZN 16CD
50106	135	BRONZE SINTER
50107		DELETED SEE 10256
50108	186	PLATING TIN LEAD (ELEC-DEPOSIT
50109		DELETED SEE 10515
50110	193	STEEL 4XXX >200 KSI
50111	138	COPPER ALLOY
50112	199	STEEL B1113 COLD ROLLED 180KSI
50113	189	STEEL 1020 SHEET <180 KSI
50114	139	COPPER TERMINAL LUG SPLICE
50116		DELETED SEE 10411
50117	32	AL 2024-T8 FORGING
50118	191	STEEL 4130 180-200KSI
50119	80	AL 6061-H13 WIRE
50120	79	AL 6053-T4 RIVET AND COLD HEADING
50121	164	CRES 430 WIRE
50122		DELETED SEE 10122
50123	193	STEEL 4XXX 200 KSI UTS
50124	185	PLATING CADMIUM
50128	57	AL 5052 HONEYCOMB CORE
50129	163	CRES 410 SHEET ANNEALED
50130	43	AL 3003-H112 BAR ROLLED
50131	189	STEEL 1009-1050 <180 KSI
50132	182	MAGNET SAMARIUM COBALT
50133	181	MAGNET CERAMIC INDOX
50134	131	BIMETAL THERMOSTATIC
50135	193	STEEL 4XXX BOLT >200 KSI
50136	130	BE-CU #10
50137	209	WELD WIRE NI-CU BASE
50138	171	CRES CUSTOM 455 H1050
50139		DELETED SEE NON-METALS
50140	168	CRES A286 FASTENERS 160KSI MIN UTS
50141	186	PLATING NICKEL LOW EMBRITTLEMENT
50142	57	AL 5052 CORE HONEYCOMB AEROWEB
50143	135	CABLE ELECTRICAL
50144	138	COPPER ALLOY 210 (95%) SHEET
50145	193	STEEL 4XXX <180 KSI UTS
50147	161	CRES 317 CONDITION 1/4 HARD
50148	81	AL 6061-O SHEET
50180	203	STEEL VASCO MATRIX
50181	108	AL 7075 FORGING
50182	204	TITANIUM 6AL 4V CASTING ANNEALED
50184	129	AL TENS-50 CASTING
50185		DELETED SEE NON-METALS
50186	134	BRONZE 70CU 10SN 20PB
50187	182	MAR-M246
50188	186	PLATING CHROMIUM GLASS
50189	188	SOLDER 5AG.16.6ZN 78.4CD
50190	138	COPPER 96 3AG NARLOY Z
50191	208	WELD WIRE INCONEL 61
50192	208	WELD WIRE INCOLOY 903
50193	139	COPPER NARLOY A
50194	133	BRAZE 75AU 20CU 5AG >200KSI
50195	132	BRAZE 50AU 25NI 25PD
50196	132	BRAZE 46RI.35AU 14NI 10PD9.5MN
50197	132	BRAZE 49RI.31AU 10PD 10NI 16MN
50198	208	WELD WIRE INCO 88 42NI 32FE 20CR
50199	133	BRAZE 75AG 20PD 5MN
50200	133	BRAZE 90AG 10PD
50201		DELETED SEE 10480
50202	1	AL 1050 NOC
50203	161	CRES 320 FILLER MATERIAL
50204	127	AL 99 F-11 (RIVET)
50205	164	CRES 419
50208	78	AL 5754 SHEET
50210	134	BRAZE DEGUSSA 5400
50212	79	AL 6060 SHEET
50213	144	CRES 13PH-8MO H950 BAR
50214	102	AL 6351 SHEET
50215	207	WELD WIRE AL 5754
50216	62	AL 5052-O SHEET
50220	16	AL 2014-T6 BAR COLD FINISHED
50221	30	AL 2024-T6 BAR COLD FINISHED
50222	33	AL 2024-T851 BAR
50224	153	CRES 300 SERIES FASTENERS
50225	163	CRES 400 SERIES FASTENERS
50226		DELETED SEE 30159
50227	147	CRES 15PH-7MO TH1050
50228		DELETED SEE 10451, 10516, 50754
50229	154	CRES 302 CONDITION B
50230	110	AL 7075-T43 SHEET
50231	189	SOLDER SN 60 PB 40
50232	173	CU,PB ANACONDA 129 AV PLATED
50233	185	PERMALLOY NI-FE ALLOY
50234	182	MANGANESE ZINC BEADS
50235	1	AISI 7MG TUNGSTEN OXIDE
50236	134	BRAZE ALLOY #8 3NI 62CU 35AU
50237	87	AL 6061-T62 STRIP
50238	64	AL 5056-H38 SHEET
50239	117	AL 7075-T73 SHEET
50240	76	AL 5556
50241	81	AL 6061-T3 SHEET
50242	71	AL 518
50243	207	WELD ELECTRODE 20CU 80AL CUPAL
50244	137	COPPER 63 ZN37 SHEET
50246	190	STEEL 1050 SHEET >180 KSI
50247	203	TITANIUM 4AL 4MO 2SN .5SI BAR
50248	9	AL 2011-T3 BAR
50249	11	AL 2011-T8 BAR
50250		DELETED SEE 50662, 50214
50251	19	AL 2014-T62 SHEET CLAD
50252		DELETED SEE 10421, 50666, 50667
50253	22	AL 2017-T451 BAR ROLLED
50254	22	AL 2017-T42 BAR ROLLED
50255	21	AL 2017-T4 BAR ROLLED

MSFC-HDBK-527 REV F 9999942 0005083 9

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
50256	25	AL 2024-T3 SHEET CLAD
50257	27	AL 2024-T36 SHEET CLAD
50258	29	AL 2024-T4 SHEET CLAD
50259	30	AL 2024-T42 SHEET CLAD
50260	31	AL 2024-T6 SHEET CLAD
50262	34	AL 2024-T86 PLATE CLAD
50263	26	AL 2024-T351 SHEET CLAD
50264	33	AL 2024-T851 PLATE CLAD
50265	23	AL 2024-F SHEET CLAD
50266	28	AL 2024-T4 FASTENERS ONLY
50267	28	AL 2024-T4 BAR ROLLED
50268	29	AL 2024-T4 SHEET
50269	80	AL 6061-O BAR ROLLED
50270	53	AL 356.0-T7 CASTING MOLD
50271	59	AL 5052-H34 SHEET
50272		DELETED SEE 10115, 50609
50273		DELETED SEE 50271, 50608
50274	61	AL 5052-H38 SHEET
50275	64	AL 5056-O BAR ROLLED
50276	78	AL 6005-H34 TUBE
50277	58	AL 5052-H24 SHEET
50278	88	AL 6061-T651 SHEET
50279	92	AL 6063-T52 BAR EXTRUDED
50280		DELETED SEE 51433, 51431, 51432
50281		DELETED SEE 10421, 50666, 50667
50282	122	AL 7175-T736 FORGING HAND
50283	122	AL 7175-T73652 FORGING HAND
50284	105	AL 7005-T62 SHEET
50285	139	COPPER FOIL 99.75CU
50286	86	AL 6061-T6 STRIP
50287	105	AL 7005-O SHEET
50288	105	AL 7005-F SHEET
50289	105	AL 7005-T6 SHEET
50290	105	AL 7005-O BAR EXTRUDED
50291	105	AL 7005-T53 BAR EXTRUDED
50292	105	AL 7005-T6 BAR EXTRUDED
50293	105	AL 7005-T63 BAR EXTRUDED
50294	121	AL 7175-O FORGING HAND
50295	139	COPPER SE F-20
50296	57	AL 5052 SHEET ANNEALED
50297	43	AL 3003 SHEET CLAD
50298	4	AL 1100 SHEET CLAD
50299	89	AL 6061-T6511 BAR EXTRUDED
50300	188	SOLDER 60SN WRAP 2
50303	138	COPPER ALLOY 220 (90%) SHEET
50304	130	BE-CU #170
50305	183	MONEL 405
50308	200	STEEL CARPENTER 49 47FE 50NI
50309		DELETED SEE 50227
50310	131	BRASS BAR
50311	135	BRONZE BAR
50312		DELETED SEE 10256, 10271, 50961, 50962
50364	173	ELGILOY
50365	154	CRES 302 STRIP 1/2 HARD
50366	154	CRES 302 SHEET 1/2 HARD
50367	157	CRES 304 SHEET ANNEALED THRU 1/2 HARD
50368	43	AL 3003 CLAD W/AL 4343
50501	57	AL 5052 RIVET
50502	152	CRES 203EZ BAR ANNEALED
50503	164	CRES 420
50504	138	COPPER 661/SIL ALLOY ROD
50505	173	DURONZE III (708)
50506	135	CABLE CLAMP AL 6061-T6
50507	136	CLAMP CABLE AL 2024-T4
50508	185	NILSTAIN BRIDGEWIRE
50509	117	AL 7075-T73 TUBE EXTRUDED
50511	188	SOLDER SILVER CASTOLIN 1030
50512	161	CRES 316L CASTING INVESTMENT ANNEALED
50513	53	AL 357.0-T6 CASTING
50514	185	NITRONIC 40
50515	153	CRES 301 SHEET 1/4 HARD
50516	53	AL 356.0-T6 CASTINGS SAND
50517	40	AL 2219-T81 TUBE
50518	194	STEEL 52100 TUBE 180-200 KSI
50519	193	STEEL 50100 BEARING 180-200 KSI
50520	194	STEEL 8620 CAS-HD TUBE >200 KSI
50521	194	STEEL 8620 CAS-HD FORGING >200 KSI
50522	190	STEEL 1117 COLD FINISH <180KSI
50523	190	STEEL 1113 COLD FINISH <180KSI
50524	107	AL 7050-T73651 & T76 SHEET & PLATE
50525	105	AL 7005-T53 WIRE EXTRUDED
50526	105	AL 7005-T6 ROD EXTRUDED
50527	105	AL 7005-T6 WIRE EXTRUDED
50528	105	AL 7005-T63 ROD EXTRUDED
50529	105	AL 7005-T63 WIRE EXTRUDED
50530	105	AL 7005-O ROD EXTRUDED
50531	105	AL 7005-O WIRE EXTRUDED
50532	4	AL 1100 ROD
50533	4	AL 1100 WIRE
50534	7	AL 1100-O PLATE
50536	9	AL 2011-T3 WIRE
50537	10	AL 2011-T6 ROD
50538	11	AL 2011-T6 WIRE
50539	11	AL 2011-T8 ROD
50540	11	AL 2011-T8 WIRE
50541	17	AL 2014-T6 PLATE CLAD
50542	18	AL 2014-T62 PLATE CLAD
50543	22	AL 2017-T4 ROD ROLLED
50544	22	AL 2017-T4 WIRE ROLLED
50545	22	AL 2017-T42 ROD ROLLED
50546	22	AL 2017-T42 WIRE ROLLED
50547	23	AL 2017-T451 ROD ROLLED
50549	21	AL 2017-O ROD ROLLED
50550	21	AL 2017-O WIRE ROLLED
50551	23	AL 2024-F PLATE CLAD
50552	25	AL 2024-T3 ROD EXTRUDED
50553	26	AL 2024-T3 WIRE EXTRUDED
50554	25	AL 2024-T3 TUBE DRAWN SEAMLESS
50555	25	AL 2024-T3 PLATE CLAD
50556	25	AL 2024-T3 PLATE

MSFC-HDBK-527 REV F ■ 9999942 0005084 0 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
50557	26	AL 2024-T351 PLATE CLAD
50558	26	AL 2024-T351 PLATE
50559	27	AL 2024-T36 PLATE CLAD
50560	29	AL 2024-T4 ROD ROLLED
50561	29	AL 2024-T4 WIRE ROLLED
50562	29	AL 2024-T4 TUBE
50563	28	AL 2024-T4 PLATE CLAD
50564	28	AL 2024-T4 PLATE
50565	30	AL 2024-T42 PLATE CLAD
50566	31	AL 2024-T6 WIRE COLD FINISHED
50567	31	AL 2024-T6 PLATE CLAD
50568	32	AL 2024-T6X ROD EXTRUDED
50569	32	AL 2024-T6X WIRE EXTRUDED
50570	31	AL 2024-T62 PLATE
50571	35	AL 2024-T8X ROD EXTRUDED
50572	35	AL 2024-T8X WIRE EXTRUDED
50573	35	AL 2024-T8X PLATE
50574	33	AL 2024-T81 SHEET CLAD
50575	32	AL 2024-T81 PLATE
50576	33	AL 2024-T851 SHEET CLAD
50577	34	AL 2024-T8510 ROD EXTRUDED
50578	34	AL 2024-T8510 WIRE EXTRUDED
50579	34	AL 2024-T86 SHEET CLAD
50580	25	AL 2024-O WIRE ROLLED
50581	24	AL 2024-O SHEET CLAD
50582	36	AL 2117-H13 WIRE RIVET AND COLD HEADING
50583	36	AL 2117-T4 WIRE RIVET AND COLD HEADING
50584	37	AL 2219-T31 PLATE
50585	38	AL 2219-T3511 ROD EXTRUDED
50586	39	AL 2219-T3511 WIRE EXTRUDED
50587	39	AL 2219-T37 PLATE
50588	39	AL 2219-T42 PLATE
50589	39	AL 2219-T62 PLATE
50590	39	AL 2219-T6 FORGING DIE
50591	42	AL 2219-T8X PLATE
50592	41	AL 2219-T851 SHEET
50593	41	AL 2219-T8511 ROD EXTRUDED
50594	41	AL 2219-T8511 SHAPES EXTRUDED
50595	42	AL 2219-T87 PLATE
50596	42	AL 2419-T8XX PLATE
50597	44	AL 3003-H112 ROD ROLLED
50598	49	AL 3003-O WIRE ROLLED
50599	43	AL 3003 STRIP
50600	47	AL 3003-O PLATE
50601	43	AL 3003 FOIL
50602	47	AL 3003-O BAR EXTRUDED
50603	48	AL 3003-O WIRE EXTRUDED
50604	57	AL 5052 ROD
50605	57	AL 5052 WIRE
50606	58	AL 5052-H24 PLATE
50607	58	AL 5052-H32 PLATE
50608	59	AL 5052-H34 PLATE
50609	60	AL 5052-H36 PLATE
50610	61	AL 5052-H38 PLATE
50611	61	AL 5052-O PLATE
50612	63	AL 5056 ROD
50613	63	AL 5056 WIRE
50614	64	AL 5056-H38 PLATE
50615	64	AL 5056-O WIRE ROLLED
50616	64	AL 5083-H111 ROD EXTRUDED
50617	65	AL 5083-H111 WIRE EXTRUDED
50618	65	AL 5083-H32 PLATE
50619	74	AL 5456-H111 ROD EXTRUDED
50620	74	AL 5456-H111 WIRE EXTRUDED
50621	75	AL 5456-H112 ROD EXTRUDED
50622	75	AL 5456-H112 WIRE EXTRUDED
50623	75	AL 5456-H112 PLATE
50624	75	AL 5456-H321 PLATE
50625	75	AL 5456-H323 PLATE
50626	75	AL 5456-H343 PLATE
50627	77	AL 5652 STRIP
50628	78	AL 5754 PLATE
50629	79	AL 6060 PLATE
50631	79	AL 6061 PLATE ANNEALED
50632	80	AL 6061-O ROD DRAWN
50633	82	AL 6061-T4 WIRE COLD FINISHED
50634	82	AL 6061-T4 SHAPES DRAWN
50635	80	AL 6061-H13 ROD RIVET AND COLD HEADING
50636	80	AL 6061-H13 WIRE RIVET AND COLD HEADING
50637	81	AL 6061-T3 PLATE
50638	84	AL 6061-T4511 ROD EXTRUDED
50639	84	AL 6061-T4511 WIRE EXTRUDED
50640	82	AL 6061-T4 ROD ROLLED
50641	82	AL 6061-T4 SHAPES ROLLED
50642	82	AL 6061-T4 PLATE
50643	85	AL 6061-T6 ROD EXTRUDED
50644	86	AL 6061-T6 WIRE EXTRUDED
50645	85	AL 6061-T6 PLATE
50646	88	AL 6061-T651 PLATE
50647	88	AL 6061-T651 STRIP
50648	89	AL 6061-T6511 ROD EXTRUDED
50649	89	AL 6061-T6511 WIRE EXTRUDED
50650	86	AL 6061-T6 SHAPE ROLLED
50651	86	AL 6061-T6 ROD ROLLED
50652	80	AL 6061-O ROD ROLLED
50653	81	AL 6061-O WIRE EXTRUDED
50654	80	AL 6061-O PLATE
50655	91	AL 6063-T42 ROD EXTRUDED
50656	92	AL 6063-T42 WIRE EXTRUDED
50657	92	AL 6063-T52 ROD EXTRUDED
50658	92	AL 6063-T52 WIRE EXTRUDED
50659	97	AL 6101 FORMS STRUCTURAL METAL
50660	100	AL 6262 ROD
50661	100	AL 6262 WIRE
50662	102	AL 6351 PLATE
50663	110	AL 7075-T43 PLATE
50664	110	AL 7075-T43 ROD EXTRUDED
50665	114	AL 7075-T62 WIRE EXTRUDED
50666	119	AL 7075-T73511 ROD EXTRUDED
50667	119	AL 7075-T73511 WIRE EXTRUDED

MSFC-HDBK-527 REV F ■ 9999942 0005085 2 ■

Information Handling Services, 2000

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
50668	119	AL 7075-T73XX ROD ROLLED DRAWN
50669	118	AL 7075-T7351 PLATE
50671	121	AL 7075-T76X PLATE CLOSE TOLERANCE
50672	120	AL 7075-T762 PLATE CLAD
50673	120	AL 7075-T7651 PLATE CLAD
50674	110	AL 7075-O WIRE ROLLED
50675	126	AL 7178-T76XX PLATE CLOSE TOLERANCE
50676	127	AL 800 SPHERES
50677	128	AL BRONZE #614 FORGING 70 KSI
50678	129	AL BRONZE #630 FORGING 70 KSI
50679	129	AL BRONZE #642 FORGING 70 KSI
50680	129	AL BRONZE #623 FORGING
50681	129	AL BRONZE #630 BAR 110 KSI
50682	129	AL BRONZE #630 FORGING 110 KSI
50683	130	AM 350 SCT 100 STRIP
50684	130	AM 350 SCT 850 STRIP
50685	130	AM 355 SCT 1000 BAR
50686	171	CRES GREEK ASCOLOY FORGING QUENCHED AND TEMPERED
50687	172	CRES GREEK ASCOLOY TUBE QUENCHED & TEMPERED
50688	130	BE 2% BEO PLATE
50689	130	BE 2% BEO BAR
50690	130	BE 2% BEO FORGING
50691	130	BE 2% BEO EXTRUSIONS
50692	131	BRASS STRIP
50693	134	BRAZE COPPER FLAT SHAPES
50694	135	BRONZE PLATE
50695	135	BRONZE SHEET
50696	135	BRONZE STRIP
50697	135	BRONZE WIRE
50698	136	CB C129Y STRIP ANNEALED
50699	136	CB FS 85 PLATE
50700	136	CB BAR
50701	136	CB WIRE
50702	135	CB 103 SHEET ANNEALED
50703	135	CB 103 PLATE
50704	136	CB 752 STRIP ANNEALED
50705		DELETED SEE 10125
50706	169	CRES A286 WIRE
50707		DELETED SEE 10125
50708	169	CRES A286 TUBE 140KSI
50709	168	CRES A286 PLATE 140KSI UTS
50710	171	CRES E-BRITE Z6-1 SHAPE
50711	171	CRES E-BRITE Z6-1 WIRE
50712	129	AL BRONZE #639
50713	141	CRES 13PH-8MO H1000 FORGING
50714	142	CRES 13PH-8MO H1025 FORGING
50715	143	CRES 13PH-8MO H1100 FORGING
50716	144	CRES 13PH-8MO H950 FORGING
50717	168	CRES A286 SHEET W/AL 800
50718	142	CRES 13PH-8MO H1050 FORGING
50719	145	CRES 14PH-8MO H1050 STRIP
50720	145	CRES 15PH-5MO H1025 FORGING
50721	156	CRES 304 FORGING (CRES 30304)
50722		DELETED SEE 50776
50723	146	CRES 15PH-5MO H1025 FORGING
50724		DELETED SEE 50810
50725		DELETED SEE 50811
50726	146	CRES 15PH-5MO H1075 FORGING
50727	146	CRES 15PH-5MO H1150 FORGING
50728	147	CRES 15PH-5MO PLATE
50729	147	CRES 15PH-7MO STRIP
50730	147	CRES 15PH-7MO PLATE
50731	148	CRES 17PH-4MO H1025 ROD
50732	148	CRES 17PH-4MO H1025 RING
50733	148	CRES 17PH-4MO H1025 PLATE
50734	148	CRES 17PH-4MO H1025 STRIP
50735	148	CRES 17PH-4MO H1050 FORGING
50736	148	CRES 17PH-4MO H1050 TUBE
50737	149	CRES 17PH-4MO H1150 FORGING EXTRUDED
50738	149	CRES 17PH-4MO H1150 ROD
50739	149	CRES 17PH-4MO H1150 FORGING
50740	149	CRES 17PH-4MO H1150M RING
50741	149	CRES 17PH-4MO H1150M FORGING
50742	149	CRES 17PH-4MO H1150M FORGING EXTRUDED
50743	149	CRES 17PH-4MO H1150M PLATE
50744	149	CRES 17PH-4MO H1150M STRIP
50746	149	CRES 17PH-4MO H900 FORGING
50747	149	CRES 17PH-4MO H900 TUBE
50748	149	CRES 17PH-4MO H950 FORGING
50749	150	CRES 17PH-4MO H950 TUBE
50750	150	CRES 17PH-7MO CH900 STRIP
50752	150	CRES 17PH-7MO PLATE CONDITION A
50753	151	CRES 17PH-7MO STRIP CONDITION A
50754	151	CRES 17PH-7MO STRIP CONDITION C
50755	150	CRES 17PH-7MO RH900 PLATE
50756	150	CRES 17PH-7MO RH900 STRIP
50757	151	CRES 17PH-7MO TH1050 FORGING
50758	151	CRES 17PH-7MO TH1100 PLATE
50759	152	CRES 21-6-9 FORGING ANNEALED
50760	153	CRES 21-6-9 RINGS ANNEALED
50761	153	CRES 21-6-9 PLATE ANNEALED
50762	153	CRES 21-6-9 STRIP ANNEALED
50763	153	CRES 301 STRIP ANNEALED 1/2 HARD 125 KSI
50764	153	CRES 301 SHEET FULL HARD
50765	154	CRES 301 STRIP FULL HARD
50766	153	CRES 301 PLATE 1/4 HARD
50767	153	CRES 301 STRIP 1/4 HARD
50768	154	CRES 302 ROD
50769	154	CRES 302 SHAPES
50770	154	CRES 302 FORGING
50771	154	CRES 302 PLATE
50772	154	CRES 302 STRIP
50773	155	CRES 303 FORGING FREE MACHINE
50774	155	CRES 303 WIRE
50775	156	CRES 304 FORGING ANNEALED
50776	157	CRES 304 TUBE ANNEALED
50777	157	CRES 304 SHEET ANNEALED
50778	157	CRES 304 STRIP ANNEALED
50779	156	CRES 304 SHAPE CONDITION B
50780	156	CRES 304 FORGING CONDITION B

MSFC-HDBK-527 REV F 9999942 0005086 4

MATCD	PAGE	DESIGNATION
50781	157	CRES 304 WIRE CONDITION B
50782	156	CRES 304 PLATE HARD
50783	157	CRES 304 STRIP HARD
50784	157	CRES 304 SHEET
50785	157	CRES 304 STRIP
50786	157	CRES 304L FORGING
50787	158	CRES 304L TUBE
50788	158	CRES 304L FORGING ANNEALED VM
50789	158	CRES 304L ROD ANNEALED VM
50790	158	CRES 304L PLATE ANNEALED
50791	158	CRES 304L STRIP ANNEALED
50792	161	CRES 316L WIRE SCREEN
50793	158	CRES 305 PLATE
50794	158	CRES 305 STRIP
50795	159	CRES 310 PLATE ANNEALED
50796	159	CRES 310 STRIP ANNEALED
50797	159	CRES 310 SHAPE
50798	159	CRES 310 FORGING
50799	160	CRES 316 PLATE ANNEALED
50800	160	CRES 316 STRIP ANNEALED
50801	161	CRES 316L PLATE ANNEALED
50802	161	CRES 316L STRIP ANNEALED
50803	161	CRES 316L SHAPE ANNEALED
50804	161	CRES 316L FORGING ANNEALED
50805	161	CRES 316L WIRE ANNEALED
50806	161	CRES 321 FORGING ANNEALED
50807	162	CRES 321 TUBE ANNEALED
50808	161	CRES 321 PLATE ANNEALED
50809	162	CRES 321 STRIP ANNEALED
50810	162	CRES 347 PLATE ANNEALED
50811	162	CRES 347 STRIP ANNEALED
50812		DELETED SEE 52775
50814	163	CRES 410 PLATE ANNEALED
50815	163	CRES 410 STRIP
50816	165	CRES 431 FORGING PANCAKE QUENCHED AND TEMPERED
50817	165	CRES 431 BAR QUENCHED AND TEMPERED
50818	166	CRES 440 PLATE
50819	165	CRES 440 BAR
50820	166	CRES 440 ROD
50821	166	CRES 440B BAR ANNEALED
50822	166	CRES 440C BAR ANNEALED
50823	166	CRES 440B BAR QUENCHED & TEMPERED
50824	167	CRES 440C CASTINGS INVESTMENT QUENCHED & TEMPERED
50825	167	CRES 440C FORGING ANNEALED
50826	138	COPPER ALLOY 110 STRIP
50827	138	COPPER ALLOY 110 PLATE
50828	138	COPPER ALLOY 110 ROD
50829	138	COPPER ALLOY 110 BAR
50830	138	COPPER ALLOY 210 (95%) STRIP
50831	138	COPPER ALLOY 220 (90%) STRIP
50832	139	COPPER ROD ANNEALED HARD TEMPER
50833	139	COPPER SHAPES ANNEALED HARD TEMPER
50834	139	COPPER ROD BUS TYPE 1
50835	139	COPPER SHAPES BUS TYPE 1
50836	139	COPPER SHAPES
50837	137	COPPER 100% PLATE ANNEALED
50838	137	COPPER 100% STRIP ANNEALED
50839	137	COPPER 661/SIL ALLOY BAR
50840	138	COPPER 661/SIL ALLOY SHAPE
50841	137	COPPER 63 ZN37 ROD
50842	173	ELGILOY RC55 STRIP SPRING
50843	174	HASTELLOY B FORGING
50844	174	HASTELLOY X STRIP
50845	174	HASTELLOY X PLATE
50846	174	HAYNES 188 FORGING ANNEALED
50847	174	HAYNES 188 PLATE ANNEALED
50848	174	HAYNES 25 FORGING ANNEALED
50849	174	HAYNES 25 PLATE ANNEALED
50850	200	STEEL H-11 FORGING >200 KSI
50851	180	INCONEL X750 PLATE ANNEALED
50852	180	INCONEL X750 FORGING STA
50853	180	INCONEL X750 RINGS STA
50854	180	INCONEL X750 PLATE STA
50855	177	INCONEL 600 FORGING ANNEALED
50856	177	INCONEL 600 RINGS ANNEALED
50857	177	INCONEL 600 PLATE ANNEALED
50858	177	INCONEL 600 STRIP ANNEALED
50859	178	INCONEL 601 PLATE ANNEALED
50860	178	INCONEL 601 STRIP ANNEALED
50861	178	INCONEL 625 FORGING ANNEALED
50862	178	INCONEL 625 PLATE ANNEALED
50863	178	INCONEL 625 PLATE
50865	181	MAGNET NI-FE ALLOY BAR
50866	182	MAGNET NI-FE STRIP MUMETAL
50867	181	MAGNET 50NI 50FE FORGING
50868	181	MAGNET 50NI 50FE TUBE
50869	184	NICKEL FL WIRE (ELECTRONIC)
50870	185	NICKEL STRIP (ELECTRONIC)
50871	179	INCONEL 718 FORGING ST1900F
50872	179	INCONEL 718 RINGS ST1900F
50873	179	INCONEL 718 RINGS ST1775F
50874	179	INCONEL 718 FORGING ST1750F
50875	179	INCONEL 718 RING ST1750F
50876	185	NICKEL U-500 ST FORGING
50877	178	INCONEL 706 PLATE
50878	178	INCONEL 706 STRIP
50879	178	INCONEL 706 FORGING STA
50880	178	INCONEL 706 RINGS STA
50881	179	INCONEL 718 FORGING CEVM
50882	179	INCONEL 718 PLATE CEVM 1900F
50883	180	INCONEL 718 STRIP CEVM ST1900F
50884	179	INCONEL 718 PLATE ST1750F
50885	180	INCONEL 718 STRIP ST1750F
50886	179	INCONEL 718 PLATE ST1900F
50887	180	INCONEL 718 STRIP ST1900F
50888	182	MAGNET NI-FE ALLOY FORGING NI77 CU5 CR1.5
50890	184	NICKEL 200 STRIP LOW CARBON
50891	184	NICKEL 201 SHEET LOW CARBON
50892	184	NICKEL 201 STRIP LOW CARBON
50893	187	RENE 41 FORGING

MSFC-HDBK-527 REV F 9999942 0005087 6

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
50894	187	RENE 41 RINGS
50895	187	RENE 41 STRIP
50896	187	RENE 41 PLATE
50897	187	RENE 95 SHAPE
50898	187	RENE 95 FORGING
50899	201	STEEL SHEET LOW CARBON 180-200 KSI
50900	202	STEEL TOOL FORGING M50 RC58-64
50901	189	STEEL 1020 PLATE <180 KSI
50902	189	STEEL 1025 SHEET <180 KSI
50903	189	STEEL 1025 PLATE <180 KSI
50904	190	STEEL 1050 PLATE >180 KSI
50905	190	STEEL 1050 STRIP >180 KSI
50906	190	STEEL 17-22A
50911	191	STEEL 4130 FORGING 125-180 KSI
50912	191	STEEL 4130 PLATE 125-180 KSI
50913	192	STEEL 4140 FORGING <201 KSI
50914	192	STEEL 4140 RING <201 KSI
50915	192	STEEL 4330V FORGING >200 KSI
50916	193	STEEL 4340 FORGING ANNEALED
50917	193	STEEL 4340 TUBE ANNEALED
50918		DELETED SEE 50922
50920	193	STEEL 4340 FORGING >200 KSI
50921	193	STEEL 4340 TUBE >200 KSI
50922	192	STEEL 4340 FORGING 180-200 KSI
50924	193	STEEL 4340 PLATE >200 KSI
50925	193	STEEL 50100 FORGING 180-200 KSI
50926	193	STEEL 52100 FORGING 180-200 KSI
50927	195	STEEL 8740 FORGING >200 KSI
50928	195	STEEL 8740 RING >200 KSI
50929	197	STEEL 9NI 4CO (.20C) FORGING 180-200 KSI
50930	197	STEEL 9NI 4CO (.20C) RING 180-200 KSI
50931	197	STEEL 9NI 4CO (.20C) FORGING 190 KSI
50932	197	STEEL 9NI 4CO (.20C) STRIP 190 KSI
50933	197	STEEL 9NI 4CO (.20C) PLATE 190 KSI
50934	197	STEEL 9NI 4CO (.30C) FORGING 180-200 KSI
50935	195	STEEL 9310 FORGING
50936	196	STEEL 9310 TUBE
50937	206	TITANIUM COMM PURE FORGING ANNEALED 70 KSI
50938	206	TITANIUM COMM PURE RINGS ANNEALED 70 KSI
50940	206	TITANIUM COMM PURE STRIP ANNEALED 55 KSI
50941	206	TITANIUM COMM PURE PLATE ANNEALED 55 KSI
50942	206	TITANIUM COMM PURE ROD 55KSI
50943	206	TITANIUM COMM PURE SHAPES 55KSI
50944	204	TITANIUM 5AL 2.5SN ROD EXTRUDED ANNEALED
50945	204	TITANIUM 5AL 2.5SN STRIP ANNEALED
50946	204	TITANIUM 5AL 2.5SN SHEET ANNEALED
50947	205	TITANIUM 6AL 4V ROD EXTRUDED ANNEALED
50948	205	TITANIUM 6AL 4V STRIP ANNEALED
50949	205	TITANIUM 6AL 4V PLATE ANNEALED
50950	205	TITANIUM 6AL 4V STRIP
50951	205	TITANIUM 6AL 4V PLATE
50952	205	TITANIUM 6AL 4V ROD ANNEALED
50953	205	TITANIUM 6AL 4V FORGING STA
50954	205	TITANIUM 6AL 4V ROD EXTRUDED STA
50955	206	TITANIUM 6AL 6V 2SN FORGING ANNEALED
50956	206	TITANIUM 6AL 6V 2SN PLATE ANNEALED
50957	206	TITANIUM 6AL 6V 2SN STRIP ANNEALED
50958	105	AL 7005-T53 ROD EXTRUDED
50959	131	BE-CU #175 SHEET
50960	131	BE-CU #175 PLATE
50961	131	BE-CU #173 ROD
50962	131	BE-CU #173 WIRE
50963	106	AL 7050-O FORGING HAND
50964	106	AL 7050-O FORGING DIE
50965	107	AL 7050-T736 FORGING DIE
50966	106	AL 7050-T411 FORGING DIE
50968	93	AL 6063-T6 WIRE EXTRUDED
50969	93	AL 6063-T6 ROD EXTRUDED
50970	92	AL 6063-T6 BAR EXTRUDED
50971	93	AL 6063-T6 SHAPES EXTRUDED
50972	93	AL 6063-T6 TUBE EXTRUDED
50973	33	AL 2024-T851 PLATE
50974	6	AL 1100-H14 PLATE
50975	6	AL 1100-H14 SHEET
50976	107	AL 7050-T73652 FORGING DIE
50977	35	AL 2048-T851 PLATE
50978	130	AL X5090
50979	127	AL A201.0-T4 CASTINGS SPECIAL MOLD
50980	127	AL A201.0-T7 CASTINGS
50981	51	AL 354.0-T4 CASTINGS PERMANENT MOLD
50982	52	AL 354.0-T6 CASTINGS PERMANENT MOLD
50983	52	AL 354.0-T61 CASTINGS PERMANENT MOLD
50984	52	AL 354.0-T62 CASTINGS PERMANENT MOLD
50985	128	AL A357.0-T6 CASTINGS SAND
50986	128	AL A357.0-T61 CASTINGS
50987	105	AL 7005-T53 SHAPES EXTRUDED
50988	105	AL 7005-T53 TUBE EXTRUDED
50989	98	AL 6151-T6 FORGING DIE
50990	98	AL 6151-T6 RINGS ROLLED
50991	98	AL 6151-T652 RINGS ROLLED
50992	126	AL 7475-T61 SHEET CLAD
50993	68	AL 5086-O SHEET
50994	68	AL 5086-O PLATE
50995	67	AL 5086-H32 SHEET
50996	67	AL 5086-H32 PLATE
50997	67	AL 5086-H34 SHEET
50998	67	AL 5086-H34 PLATE
50999	67	AL 5086-H36 SHEET
51000	68	AL 5086-H38 SHEET
51001	67	AL 5086-H112 SHEET
51002	66	AL 5086-H112 PLATE
51003	67	AL 5086-H116 SHEET
51004	67	AL 5086-H116 PLATE
51005	68	AL 5086-O WIRE EXTRUDED
51006	68	AL 5086-O ROD EXTRUDED
51007	68	AL 5086-O BAR EXTRUDED
51008	68	AL 5086-O SHAPES EXTRUDED
51009	68	AL 5086-O TUBE EXTRUDED
51010	66	AL 5086-H111 WIRE EXTRUDED
51011	66	AL 5086-H111 ROD EXTRUDED

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005088 8 ■

MATCD	PAGE	DESIGNATION
51012	66	AL 5086-H111 BAR EXTRUDED
51013	66	AL 5086-H111 SHAPES EXTRUDED
51014	66	AL 5086-H111 TUBE EXTRUDED
51015	67	AL 5086-H112 WIRE EXTRUDED
51016	66	AL 5086-H112 ROD EXTRUDED
51017	66	AL 5086-H112 BAR EXTRUDED
51018	67	AL 5086-H112 SHAPES EXTRUDED
51019	67	AL 5086-H112 TUBE EXTRUDED
51020	68	AL 5086-O TUBE DRAWN SEAMLESS
51021	67	AL 5086-H32 TUBE DRAWM SEAMLESS
51022	67	AL 5086-H34 TUBE DRAWN SEAMLESS
51023	67	AL 5086-H36 TUBE DRAWN SEAMLESS
51024	68	AL 5086-O TUBE WELDED
51025	67	AL 5086-H32 TUBE WELDED
51026	67	AL 5086-H34 TUBE WELDED
51027	68	AL 5086-H36 TUBE WELDED
51028	68	AL 5086-O PIPE
51029	66	AL 5086-H111 PIPE
51031	66	AL 5086-H112 PIPE
51044	9	AL 1345
51045	128	AL A356.0-T6 CASTINGS
51046	37	AL 2219-O SHEET
51047	37	AL 2219-O PLATE
51048	40	AL 2219-T851 BAR ROLLED
51049	41	AL 2219-T851 ROD ROLLED
51050	37	AL 2219-O WIRE EXTRUDED
51051	37	AL 2219-O ROD EXTRUDED
51052	37	AL 2219-O BAR EXTRUDED
51053	37	AL 2219-O SHAPES EXTRUDED
51054	37	AL 2219-O TUBE EXTRUDED
51055	38	AL 2219-T31 WIRE EXTRUDED
51056	37	AL 2219-T31 ROD EXTRUDED
51057	37	AL 2219-T31 BAR EXTRUDED
51058	38	AL 2219-T31 SHAPES EXTRUDED
51059	38	AL 2219-T31 TUBE EXTRUDED
51060	38	AL 2219-T3510 WIRE EXTRUDED
51061	38	AL 2219-T3510 ROD EXTRUDED
51062	38	AL 2219-T3510 BAR EXTRUDED
51063	38	AL 2219-T3510 SHAPES EXTRUDED
51064	38	AL 2219-T3510 TUBE EXTRUDED
51066	38	AL 2219-T3511 SHAPES EXTRUDED
51067	38	AL 2219-T3511 TUBE EXTRUDED
51068	40	AL 2219-T81 WIRE EXTRUDED
51069	40	AL 2219-T81 ROD EXTRUDED
51070	40	AL 2219-T81 BAR EXTRUDED
51071	40	AL 2219-T81 SHAPES EXTRUDED
51072	41	AL 2219-T8510 WIRE EXTRUDED
51073	41	AL 2219-T8510 ROD EXTRUDED
51074	41	AL 2219-T8510 BAR EXTRUDED
51075	41	AL 2219-T8510 SHAPES EXTRUDED
51076	41	AL 2219-T8510 TUBE EXTRUDED
51077	41	AL 2219-T8511 WIRE EXTRUDED
51078	183	MP 159
51079	41	AL 2219-T8511 TUBE EXTRUDED
51080	41	AL 2219-T8511 TUBE EXTRUDED SEAMLESS
51081	39	AL 2219-T6 RINGS ROLLED
51082	37	AL 2219-H13 WIRE RIVET AND COLD HEADING
51083	39	AL 2219-T6 WIRE RIVET AND COLD HEADING
51084	36	AL 2219-H13 ROD RIVET AND COLD HEADING
51085	39	AL 2219-T6 ROD RIVET AND COLD HEADING
51086	37	AL 2219-O WIRE RIVET AND COLD HEADING
51087	37	AL 2219-H23 WIRE RIVET AND COLD HEADING
51088	37	AL 2219-O ROD RIVET AND COLD HEADING
51089	37	AL 2219-H23 ROD RIVET AND COLD HEADING
51090	23	AL 2024-O PLATE
51091	28	AL 2024-T361 SHEET
51092	28	AL 2024-T361 PLATE
51093	35	AL 2024-T861 SHEET
51094	34	AL 2024-T861 PLATE
51095	32	AL 2024-T72 SHEET
51096	30	AL 2024-T42 SHEET
51097	29	AL 2024-T42 PLATE
51098	31	AL 2024-T6 BAR ROLLED
51099	30	AL 2024-T42 WIRE ROLLED
51100	30	AL 2024-T42 ROD ROLLED
51101	29	AL 2024-T42 BAR ROLLED
51102	32	AL 2024-T62 WIRE ROLLED
51103	31	AL 2024-T62 ROD ROLLED
51104	31	AL 2024-T62 BAR ROLLED
51105	28	AL 2024-T36 WIRE ROLLED
51106	26	AL 2024-T351 BAR ROLLED
51107	26	AL 2024-T351 ROD ROLLED
51108	33	AL 2024-T851 ROD ROLLED
51109	25	AL 2024-O WIRE EXTRUDED
51110	30	AL 2024-T42 WIRE EXTRUDED
51111	33	AL 2024-T81 WIRE EXTRUDED
51112	23	AL 2024-O BAR EXTRUDED
51113	26	AL 2024-T3510 BAR EXTRUDED
51114	27	AL 2024-T3511 BAR EXTRUDED
51115	29	AL 2024-T42 BAR EXTRUDED
51116	28	AL 2024-T4 BAR EXTRUDED
51117	24	AL 2024-O TUBE EXTRUDED
51118	26	AL 2024-T3 TUBE EXTRUDED
51119		DELETED SEE 80157
51120	27	AL 2024-T3510 TUBE EXTRUDED
51121	27	AL 2024-T3511 TUBE EXTRUDED
51122	30	AL 2024-T42 TUBE EXTRUDED
51123	33	AL 2024-T81 TUBE EXTRUDED
51124	34	AL 2024-T8510 TUBE EXTRUDED
51125	34	AL 2024-T8511 TUBE EXTRUDED
51126	29	AL 2024-T4 TUBE EXTRUDED
51127	24	AL 2024-O TUBE DRAWN SEAMLESS
51128	30	AL 2024-T42 TUBE DRAWN SEAMLESS
51129	25	AL 2024-O WIRE RIVET AND COLD HEADING
51130	23	AL 2024-H13 WIRE RIVET AND COLD HEADING
51131	29	AL 2024-T4 WIRE RIVET AND COLD HEADING
51132	23	AL 2024-H23 WIRE RIVET AND COLD HEADING
51133	24	AL 2024-O ROD RIVET AND COLD HEADING
51134	23	AL 2024-H13 ROD RIVET AND COLD HEADING
51135	29	AL 2024-T4 ROD RIVET AND COLD HEADING

MSFC-HDBK-527 REV F 9999942 0005089 T

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
51136	23	AL 2024-H23 ROD RIVET AND COLD HEADING
51137	71	AL 520.0-T4 CASTINGS SAND
51138	121	AL 712.0-T5 CASTINGS SAND
51139	35	AL 2025-T6 FORGING DIE
51140	35	AL 2025-F FORGING DIE
51141	35	AL 2025-T6 FORGING STOCK
51142	35	AL 2025-F FORGING STOCK
51143	42	AL 2618-F FORGING DIE
51144	42	AL 2618-F FORGING HAND
51145	42	AL 2618-F RINGS ROLLED
51146	42	AL 2618-T61 FORGING DIE
51147	43	AL 2618-T61 FORGING HAND
51148	24	AL 2024-O ROD EXTRUDED
51150	27	AL 2024-T3510 ROD EXTRUDED
51151	27	AL 2024-T3511 ROD EXTRUDED
51152	30	AL 2024-T42 ROD EXTRUDED
51153	34	AL 2024-T8511 ROD EXTRUDED
51154	29	AL 2024-T4 ROD EXTRUDED
51155	24	AL 2024-O SHAPES EXTRUDED
51156	25	AL 2024-T3 SHAPES EXTRUDED
51157	27	AL 2024-T3510 SHAPES EXTRUDED
51158	27	AL 2024-T3511 SHAPES EXTRUDED
51159	30	AL 2024-T42 SHAPES EXTRUDED
51160	34	AL 2024-T8511 SHAPES EXTRUDED
51161	29	AL 2024-T4 SHAPES EXTRUDED
51166	43	AL 2618-T61 FORGING STOCK
51167	129	AL KO-1 CASTINGS SAND
51168	129	AL KO-1 CASTINGS PREMIUM
51169	152	CRES 19-9DL PLATE ANNEALED
51170		DELETED SEE 52429
51171	182	MAGNET NI-FE ALLOY PLATE
51172	9	AL 1230
51173	35	AL 2036-T4 SHEET
51176	127	AL 8177
51177	127	AL 8030
51178	127	AL 8017
51179	100	AL 6253
51180	121	AL 7108
51181	9	AL 1175
51182	9	AL 1200-H112 TUBE EXTRUDED COILED
51183	78	AL 6003
51184	54	AL 4643
51185	98	AL 6105
51186	104	AL 6951
51187	105	AL 7008
51188	127	AL 8176
51189	108	AL 7072
51190	36	AL 2218-F FORGING DIE
51191	36	AL 2218-T61 FORGING DIE
51192	36	AL 2218-T72 FORGING DIE
51193	71	AL 5154-O SHEET
51194	69	AL 5154-H32 SHEET
51195	69	AL 5154-H34 SHEET
51196	70	AL 5154-H36 SHEET
51197	70	AL 5154-H38 SHEET
51198	70	AL 5154-O PLATE
51199	69	AL 5154-H32 PLATE
51200	69	AL 5154-H34 PLATE
51201	68	AL 5154-H112 PLATE
51202	54	AL 4045 METAL BRAZING FILLER
51203	28	AL 2024-T361 SHEET CLAD
51204	28	AL 2024-T361 PLATE CLAD
51205	32	AL 2024-T62 SHEET CLAD
51206	31	AL 2024-T62 PLATE CLAD
51207	32	AL 2024-T72 SHEET CLAD
51208	35	AL 2024-T861 SHEET CLAD
51209	34	AL 2024-T861 PLATE CLAD
51210	63	AL 5056-H32 WIRE RIVET AND COLD HEADING
51211	63	AL 5056-H32 ROD RIVET AND COLD HEADING
51212	63	AL 5056-H22 WIRE RIVET AND COLD HEADING
51213	63	AL 5056-H22 ROD RIVET AND COLD HEADING
51214	63	AL 5056-H111 WIRE ROLLED
51215	63	AL 5056-H12 WIRE ROLLED
51216	63	AL 5056-H32 WIRE ROLLED
51217	63	AL 5056-H14 WIRE ROLLED
51218	63	AL 5056-H34 WIRE ROLLED
51219	63	AL 5056-H18 WIRE ROLLED
51220	64	AL 5056-H38 WIRE ROLLED
51221	63	AL 5056-H192 WIRE ROLLED
51222	64	AL 5056-H392 WIRE ROLLED
51223	129	AL KO-1-T6 CASTINGS
51224	129	AL KO-1-T7 CASTINGS
51225	52	AL 356.0-T51 CASTINGS INVESTMENT
51226	53	AL 356.0-T6 CASTINGS PERMANENT MOLD
51227	53	AL 356.0-T6 CASTINGS CENTRIFUGAL
51228	53	AL 359.0-T61 CASTINGS
51229	121	AL 7149-T73 FORGING DIE
51230	121	AL 7149-T73510 EXTRUSIONS
51231	121	AL 7149-T73511 EXTRUSIONS
51232	66	AL 5083-O SHEET
51233	65	AL 5083-H321 SHEET
51234	65	AL 5083-H323 SHEET
51235	65	AL 5083-H343 SHEET
51236	66	AL 5083-O PLATE
51237	65	AL 5083-H321 PLATE
51238	65	AL 5083-H112 PLATE
51239	65	AL 5083-O BAR EXTRUDED
51240	65	AL 5083-H112 BAR EXTRUDED
51241	66	AL 5083-O ROD EXTRUDED
51242	65	AL 5083-H112 ROD EXTRUDED
51243	66	AL 5083-O WIRE EXTRUDED
51244	65	AL 5083-H112 WIRE EXTRUDED
51245	66	AL 5083-O TUBE EXTRUDED
51246	65	AL 5083-H111 TUBE EXTRUDED
51247	65	AL 5083-H112 TUBE EXTRUDED
51248	66	AL 5083-O SHAPES EXTRUDED
51249	64	AL 5083-H111 SHAPES EXTRUDED
51250	65	AL 5083-H112 SHAPES EXTRUDED
51251	64	AL 5083-H111 FORGING DIE
51252	65	AL 5083-H112 FORGING DIE

MSFC-HDBK-527 REV F ■ 9999942 0005090 6 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
51253	64	AL 5083-H111 FORGING HAND
51254	65	AL 5083-H112 FORGING HAND
51255	83	AL 6061-T451 WIRE
51256	89	AL 6061-T94 WIRE
51257	88	AL 6061-T651 WIRE
51258	89	AL 6061-T89 WIRE
51259	87	AL 6061-T62 ROD EXTRUDED
51260	87	AL 6061-T62 BAR EXTRUDED
51261	81	AL 6061-O TUBE DRAWN
51262	83	AL 6061-T42 TUBE DRAWN
51263	86	AL 6061-T6 TUBE DRAWN
51264	87	AL 6061-T62 TUBE DRAWN
51265	86	AL 6061-T6 TUBE CONDENSER
51266	81	AL 6061-O TUBE
51267	83	AL 6061-T451 TUBE
51268	86	AL 6061-T6 TUBE WELDED
51269	88	AL 6061-T651 TUBE WELDED
51270	80	AL 6061-O PIPE
51271	82	AL 6061-T4 PIPE
51272	84	AL 6061-T4510 PIPE
51273	84	AL 6061-T4511 PIPE
51274	83	AL 6061-T42 PIPE
51275	87	AL 6061-T62 PIPE
51277	88	AL 6061-T6510 PIPE
51278	89	AL 6061-T6511 PIPE
51279	87	AL 6061-T6 WIRE RIVET AND COLD HEADING
51280	86	AL 6061-T6 ROD RIVET AND COLD HEADING
51281	80	AL 6061-H23 WIRE RIVET AND COLD HEADING
51282	80	AL 6061-H23 ROD RIVET AND COLD HEADING
51283	86	AL 6061-T6 SHAPES STANDARD STRUCTURAL
51284	79	AL 6061-F FORGING STOCK
51285	81	AL 6061-T4 FORGING DIE
51286	82	AL 6061-T4 RINGS ROLLED
51287	80	AL 6061-O FOIL
51288	79	AL 6061-F SHEET
51289	83	AL 6061-T42 SHEET
51290	87	AL 6061-T62 SHEET
51291	79	AL 6061-F PLATE
51292	83	AL 6061-T42 PLATE
51293	87	AL 6061-T62 PLATE
51294	83	AL 6061-T42 BAR ROLLED
51295	87	AL 6061-T62 BAR ROLLED
51296	85	AL 6061-T6 BAR DRAWN
51297	88	AL 6061-T651 BAR DRAWN
51298	85	AL 6061-T6 BAR COLD FINISHED
51299	88	AL 6061-T651 BAR COLD FINISHED
51300	83	AL 6061-T42 ROD ROLLED
51301	87	AL 6061-T62 ROD ROLLED
51302	85	AL 6061-T6 ROD DRAWN
51303	87	AL 6061-T62 ROD DRAWN
51304	88	AL 6061-T651 ROD DRAWN
51305	85	AL 6061-T6 ROD COLD FINISHED
51306	87	AL 6061-T62 ROD COLD FINISHED
51307	88	AL 6061-T651 ROD COLD FINISHED
51308	82	AL 6061-T4 WIRE ROLLED
51309	83	AL 6061-T42 WIRE ROLLED
51310	87	AL 6061-T6 WIRE ROLLED
51311	88	AL 6061-T62 WIRE
51312	82	AL 6061-T4 WIRE DRAWN
51313	83	AL 6061-T42 WIRE DRAWN
51314	86	AL 6061-T6 WIRE DRAWN
51315	88	AL 6061-T62 WIRE DRAWN
51316	83	AL 6061-T42 SHAPES ROLLED
51317	87	AL 6061-T62 SHAPES ROLLED
51318	86	AL 6061-T6 SHAPES DRAWN
51319	88	AL 6061-T651 SHAPES DRAWN
51320	84	AL 6061-T4510 ROD EXTRUDED
51321	83	AL 6061-T42 ROD EXTRUDED
51322	80	AL 6061-O SHAPES
51323	81	AL 6061-T1 ROD EXTRUDED
51324	84	AL 6061-T51 ROD EXTRUDED
51325	88	AL 6061-T6510 ROD EXTRUDED
51326	81	AL 6061-T1 BAR EXTRUDED
51327	83	AL 6061-T4510 BAR EXTRUDED
51328	82	AL 6061-T42 BAR EXTRUDED
51329	84	AL 6061-T51 BAR EXTRUDED
51330	88	AL 6061-T6510 BAR EXTRUDED
51331	80	AL 6061-O SHAPES EXTRUDED
51332	86	AL 6061-T6 SHAPES EXTRUDED
51333	87	AL 6061-T62 SHAPES EXTRUDED
51334	81	AL 6061-T1 SHAPES EXTRUDED
51335	84	AL 6061-T4510 SHAPES EXTRUDED
51336	84	AL 6061-T4511 SHAPES EXTRUDED
51337	83	AL 6061-T42 SHAPES EXTRUDED
51338	84	AL 6061-T51 SHAPES EXTRUDED
51339	89	AL 6061-T6510 SHAPES EXTRUDED
51340	89	AL 6061-T6511 SHAPES EXTRUDED
51341	81	AL 6061-O TUBE EXTRUDED
51342	81	AL 6061-T1 TUBE EXTRUDED
51343	84	AL 6061-T4510 TUBE EXTRUDED
51344	84	AL 6061-T4511 TUBE EXTRUDED
51345	83	AL 6061-T42 TUBE EXTRUDED
51346	84	AL 6061-T51 TUBE EXTRUDED
51347	89	AL 6061-T6510 TUBE EXTRUDED
51348	89	AL 6061-T6511 TUBE EXTRUDED
51349	86	AL 6061-T6 TUBE EXTRUDED
51350	87	AL 6061-T62 TUBE EXTRUDED
51351	81	AL 6061-T1 WIRE EXTRUDED
51352	82	AL 6061-T4 WIRE EXTRUDED
51353	84	AL 6061-T4510 WIRE EXTRUDED
51354	83	AL 6061-T42 WIRE EXTRUDED
51355	85	AL 6061-T51 WIRE EXTRUDED
51356	88	AL 6061-T62 WIRE EXTRUDED
51357	89	AL 6061-T6510 WIRE EXTRUDED
51358	79	AL 6061-F FORGING DIE
51359	85	AL 6061-T6 FORGING DIE
51360	79	AL 6061-F FORGING HAND
51361	85	AL 6061-T6 FORGING HAND
51362	79	AL 6061-F RINGS ROLLED
51363	85	AL 6061-T6 RINGS ROLLED

MSFC-HDBK-527 REV F 9999942 0005091 8

Information Handling Services, 2000

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
51364	88	AL 6061-T651 RING ROLLED
51365	89	AL 6061-T652 RINGS ROLLED
51366	81	AL 6061-O TUBE DRAWN SEAMLESS
51367	80	AL 6061-F TUBE DRAWN SEAMLESS
51368	83	AL 6061-T42 TUBE DRAWN SEAMLESS
51369	85	AL 6061-T6 PIPE
51370	87	AL 6061-T61 FORGING HAND
51371	86	AL 6061-T6 SHAPES EXTRUDED STRUCTURAL
51372	80	AL 6061-O IMPACTS
51373	79	AL 6061-F IMPACTS
51374	81	AL 6061-T4 IMPACTS
51375	85	AL 6061-T6 IMPACTS
51376	89	AL 6061-T84 IMPACTS
51377	80	AL 6061-H112 IMPACTS
51378	109	AL 7075-O SHEET
51379	108	AL 7075-O PLATE
51380	113	AL 7075-T62 SHEET
51381	112	AL 7075-T62 PLATE
51382	114	AL 7075-T651 PLATE
51384	120	AL 7075-T7651 PLATE
51385	108	AL 7075-O BAR ROLLED
51386	108	AL 7075-O BAR COLD FINISHED
51387	112	AL 7075-T6 WIRE ROLLED
51388	112	AL 7075-T6 WIRE COLD FINISHED
51389	111	AL 7075-T6 ROD ROLLED
51390	111	AL 7075-T6 ROD COLD FINISHED
51391	110	AL 7075-T6 BAR ROLLED
51392	110	AL 7075-T6 BAR COLD FINISHED
51393	114	AL 7075-T62 WIRE ROLLED
51394	114	AL 7075-T62 WIRE COLD FINISHED
51395	113	AL 7075-T62 ROD ROLLED
51396	113	AL 7075-T62 ROD COLD FINISHED
51397	112	AL 7075-T62 BAR ROLLED
51398	112	AL 7075-T62 BAR COLD FINISHED
51399	115	AL 7075-T651 WIRE ROLLED
51400	115	AL 7075-T651 WIRE COLD FINISHED
51401	115	AL 7075-T651 ROD ROLLED
51402	114	AL 7075-T651 ROD COLD FINISHED
51403	114	AL 7075-T651 BAR ROLLED
51404	114	AL 7075-T651 BAR COLD FINISHED
51405	117	AL 7075-T73 WIRE ROLLED
51406	117	AL 7075-T73 WIRE COLD FINISHED
51407	117	AL 7075-T73 ROD ROLLED
51408	116	AL 7075-T73 ROD COLD FINISHED
51409	116	AL 7075-T73 BAR ROLLED
51410	116	AL 7075-T73 BAR COLD FINISHED
51411	118	AL 7075-T7351 WIRE ROLLED
51412	118	AL 7075-T7351 WIRE COLD FINISHED
51413	118	AL 7075-T7351 ROD ROLLED
51414	118	AL 7075-T7351 ROD COLD FINISHED
51415	117	AL 7075-T7351 BAR COLD FINISHED
51416	112	AL 7075-T6 WIRE DRAWN
51417	114	AL 7075-T62 WIRE DRAWN
51418	115	AL 7075-T651 WIRE DRAWN
51419	117	AL 7075-T73 WIRE DRAWN
51420	118	AL 7075-T7351 WIRE DRAWN
51421	111	AL 7075-T6 ROD DRAWN
51422	113	AL 7075-T62 ROD DRAWN
51423	115	AL 7075-T651 ROD DRAWN
51424	116	AL 7075-T73 ROD DRAWN
51425	118	AL 7075-T7351 ROD DRAWN
51426	108	AL 7075-O BAR DRAWN
51427	110	AL 7075-T6 BAR DRAWN
51428	112	AL 7075-T62 BAR DRAWN
51429	114	AL 7075-T651 BAR DRAWN
51430	116	AL 7075-T73 BAR DRAWN
51431	117	AL 7075-T73 WIRE EXTRUDED
51432	117	AL 7075-T73 ROD EXTRUDED
51433	116	AL 7075-T73 BAR EXTRUDED
51434	117	AL 7075-T73 SHAPES EXTRUDED
51435	118	AL 7075-T73510 WIRE EXTRUDED
51436	118	AL 7075-T73510 ROD EXTRUDED
51437	118	AL 7075-T73510 BAR EXTRUDED
51438	118	AL 7075-T73510 SHAPES EXTRUDED
51439	118	AL 7075-T73510 TUBE EXTRUDED
51440	119	AL 7075-T73511 SHAPES EXTRUDED
51441	120	AL 7075-T76 WIRE EXTRUDED
51442	120	AL 7075-T76 ROD EXTRUDED
51443	119	AL 7075-T76 BAR EXTRUDED
51444	120	AL 7075-T76 SHAPES EXTRUDED
51445	120	AL 7075-T76 TUBE EXTRUDED
51446	121	AL 7075-T76510 WIRE EXTRUDED
51448	120	AL 7075-T76510 BAR EXTRUDED
51449	120	AL 7075-T76510 SHAPES EXTRUDED
51450	121	AL 7075-T76510 TUBE EXTRUDED
51451	121	AL 7075-T76511 WIRE EXTRUDED
51452	121	AL 7075-T76511 ROD EXTRUDED
51453	121	AL 7075-T76511 BAR EXTRUDED
51454	121	AL 7075-T76511 SHAPES EXTRUDED
51455	121	AL 7075-T76511 TUBE EXTRUDED
51456	108	AL 7075-O BAR EXTRUDED
51457	109	AL 7075-O SHAPES EXTRUDED
51458	110	AL 7075-O TUBE EXTRUDED
51459	112	AL 7075-T6 WIRE EXTRUDED
51460	111	AL 7075-T6 ROD EXTRUDED
51461	110	AL 7075-T6 BAR EXTRUDED
51462	111	AL 7075-T6 SHAPES EXTRUDED
51463	112	AL 7075-T6 TUBE EXTRUDED
51464	113	AL 7075-T62 ROD EXTRUDED
51465	113	AL 7075-T62 SHAPES EXTRUDED
51466	113	AL 7075-T62 TUBE EXTRUDED
51467	115	AL 7075-T6510 WIRE EXTRUDED
51468	115	AL 7075-T6510 ROD EXTRUDED
51469	115	AL 7075-T6510 BAR EXTRUDED
51470	115	AL 7075-T6510 SHAPES EXTRUDED
51471	115	AL 7075-T6510 TUBE EXTRUDED
51472	116	AL 7075-T6511 WIRE EXTRUDED
51473	115	AL 7075-T6511 ROD EXTRUDED
51474	115	AL 7075-T6511 BAR EXTRUDED
51475	115	AL 7075-T6511 SHAPES EXTRUDED

MSFC-HDBK-527 REV F ■ 9999942 0005092 T ■

MATCD	PAGE	DESIGNATION
51476	116	AL 7075-T6511 TUBE EXTRUDED
51477	109	AL 7075-O TUBE DRAWN
51478	112	AL 7075-T6 TUBE DRAWN
51479	113	AL 7075-T62 TUBE DRAWN
51480	117	AL 7075-T73 TUBE DRAWN
51485	116	AL 7075-T73 FORGING DIE
51486	116	AL 7075-T652 FORGING HAND
51487	116	AL 7075-T73 FORGING HAND
51488	119	AL 7075-T74 FORGING DIE
51489	119	AL 7075-T74 FORGING HAND
51490	119	AL 7075-T7452 FORGING HAND
51491	111	AL 7075-T6 RINGS ROLLED
51492	116	AL 7075-T652 RINGS ROLLED
51493	116	AL 7075-T73 FORGING STOCK
51494	119	AL 7075-T736 FORGING
51495	108	AL 7075-O IMPACTS
51496	111	AL 7075-T6 IMPACTS
51497	108	AL 7075-H13 WIRE RIVET AND COLD HEADING
51498	108	AL 7075-H13 ROD RIVET AND COLD HEADING
51499	117	AL 7075-T73 WIRE RIVET AND COLD HEADING
51500	117	AL 7075-T73 ROD RIVET AND COLD HEADING
51501	108	AL 7075-H23 WIRE RIVET AND COLD HEADING
51502	108	AL 7075-H23 ROD RIVET AND COLD HEADING
51503	116	AL 7075-T73 IMPACTS
51504	12	AL 2014-O SHEET
51505	12	AL 2014-T3 SHEET
51506	13	AL 2014-T4 SHEET
51507	14	AL 2014-T42 SHEET
51508	17	AL 2014-T6 SHEET
51509	19	AL 2014-T62 SHEET
51510	12	AL 2014-O PLATE
51511	14	AL 2014-T42 PLATE
51512	15	AL 2014-T451 PLATE
51513	18	AL 2014-T62 PLATE
51514	19	AL 2014-T651 PLATE
51517	17	AL 2014-T6 PLATE
51520	11	AL 2014-O BAR ROLLED
51521	13	AL 2014-T4 BAR ROLLED
51522	14	AL 2014-T42 BAR ROLLED
51523	15	AL 2014-T451 BAR ROLLED
51525	18	AL 2014-T62 BAR ROLLED
51526	19	AL 2014-T651 BAR ROLLED
51527	11	AL 2014-O BAR COLD FINISHED
51528	13	AL 2014-T4 BAR COLD FINISHED
51529	14	AL 2014-T42 BAR COLD FINISHED
51530	15	AL 2014-T451 BAR COLD FINISHED
51532	18	AL 2014-T62 BAR COLD FINISHED
51533	19	AL 2014-T651 BAR COLD FINISHED
51542	121	AL 7175-T66 FORGING DIE
51543	122	AL 7175-T74 FORGING DIE
51544	122	AL 7175-T74 FORGING HAND
51545	122	AL 7175-T7452 FORGING HAND
51546	122	AL 7175-T7452 FORGING DIE
51547	122	AL 7175-T7454 FORGING DIE
51548	121	AL 7175-T73511 EXTRUSIONS
51549	12	AL 2014-O SHEET CLAD
51550	12	AL 2014-O PLATE CLAD
51551	13	AL 2014-T3 SHEET CLAD
51552	13	AL 2014-T4 SHEET CLAD
51553	15	AL 2014-T42 SHEET CLAD
51554	14	AL 2014-T42 PLATE CLAD
51555	15	AL 2014-T451 PLATE CLAD
51556	19	AL 2014-T651 PLATE CLAD
51557	52	AL 355.0-T6 CASTINGS PERMAMENT MOLD
51558	52	AL 355.0-T71 CASTINGS PERMANENT MOLD
51559	52	AL 355.0-T71 CASTINGS SAND
51560	52	AL 355.0-T6 CASTINGS SAND
51561	52	AL 355.0-T51 CASTINGS SAND
51562	126	AL 7475-T61 SHEET
51563	127	AL 7475-T761 SHEET
51564	126	AL 7475-T651 PLATE
51565	127	AL 7475-T7651 PLATE
51566	127	AL 7475-T7351 PLATE
51567	105	AL 7010-T7451 PLATE
51568	106	AL 7010-T7651 PLATE
51569	63	AL 5056-H192 WIRE ROLLED CLAD
51570	64	AL 5056-H392 WIRE ROLLED CLAD
51571	64	AL 5056-H393 WIRE ROLLED CLAD
51575	103	AL 6463-T1 WIRE EXTRUDED
51576	103	AL 6463-T1 ROD EXTRUDED
51577	103	AL 6463-T1 BAR EXTRUDED
51578	103	AL 6463-T1 SHAPES EXTRUDED
51579	103	AL 6463-T1 TUBE EXTRUDED
51580	103	AL 6463-T5 WIRE EXTRUDED
51581	103	AL 6463-T5 ROD EXTRUDED
51582	103	AL 6463-T5 BAR EXTRUDED
51583	103	AL 6463-T5 SHAPES EXTRUDED
51584	104	AL 6563-T5 TUBE EXTRUDED
51585	104	AL 6463-T6 WIRE EXTRUDED
51586	103	AL 6463-T6 ROD EXTRUDED
51587	103	AL 6463-T6 BAR EXTRUDED
51588	103	AL 6463-T6 SHAPES EXTRUDED
51589	103	AL 6463-T6 TUBE EXTRUDED
51590	9	AL 1350-H19 WIRE
51591	9	AL 1350-H14 WIRE
51592	9	AL 1350 CONDUCTOR SOLID ROUND
51593	23	AL 2018-T61 FORGING DIE
51594	50	AL 3004-O SHEET
51595	50	AL 3004-O PLATE
51596	49	AL 3004-H32 SHEET
51597	49	AL 3004-H32 PLATE
51598	49	AL 3004-H34 SHEET
51599	49	AL 3004-H34 PLATE
51600	50	AL 3004-H36 SHEET
51601	50	AL 3004-H38 SHEET
51602	49	AL 3004-H112 PLATE
51603	50	AL 3004-O TUBE EXTRUDED
51604	50	AL 3004-O TUBE WELDED
51605	49	AL 3004-H32 TUBE WELDED
51606	49	AL 3004-H34 TUBE WELDED

MSFC-HDBK-527 REV F 9999942 0005093 1

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
51607	50	AL 3004-H36 TUBE WELDED
51608	50	AL 3004-H38 TUBE WELDED
51609	48	AL 3003-O SHEET CLAD
51610	47	AL 3003-O PLATE CLAD
51611	45	AL 3003-H12 SHEET CLAD
51612	45	AL 3003-H12 PLATE CLAD
51613	45	AL 3003-H14 SHEET CLAD
51614	45	AL 3003-H14 PLATE CLAD
51615	46	AL 3003-H16 SHEET CLAD
51616	46	AL 3003-H18 SHEET CLAD
51617	43	AL 3003-H112 PLATE CLAD
51618	48	AL 3003-O TUBE DRAWN SEAMLESS CLAD
51619	46	AL 3003-H14 TUBE DRAWN SEAMLESS CLAD
51620	47	AL 3003-H18 TUBE DRAWN SEAMLESS CLAD
51621	44	AL 3003-H113 TUBE DRAWN SEAMLESS CLAD
51622	48	AL 3003-O TUBE EXTRUDED CLAD
51623	44	AL 3003-H112 TUBE EXTRUDED CLAD
51624	46	AL 3003-H14 TUBE CONDENSER CLAD
51625	47	AL 3003-H25 TUBE CONDENSER CLAD
51626	48	AL 3003-O TUBE WELDED CLAD
51627	45	AL 3003-H12 TUBE WELDED CLAD
51628	46	AL 3003-H14 TUBE WELDED
51629	44	AL 3003-H112 TUBE WELDED CLAD
51630	104	AL 7001-O ROD EXTRUDED
51631	104	AL 7001-O BAR EXTRUDED
51632	104	AL 7001-O SHAPES EXTRUDED
51633	104	AL 7001-T6 ROD EXTRUDED
51634	104	AL 7001-T6 BAR EXTRUDED
51635	104	AL 7001-T6 SHAPES EXTRUDED
51636	104	AL 7001-T62 ROD EXTRUDED
51637	104	AL 7001-T62 BAR EXTRUDED
51638	104	AL 7001-T62 SHAPES EXTRUDED
51639	104	AL 7001-T6510 ROD EXTRUDED
51640	104	AL 7001-T6510 BAR EXTRUDED
51641	104	AL 7001-T6510 SHAPES EXTRUDED
51642	104	AL 7001-T6511 ROD EXTRUDED
51643	104	AL 7001-T6511 BAR EXTRUDED
51644	105	AL 7001-T6511 SHAPES EXTRUDED
51645	56	AL 5005-O SHEET
51646	55	AL 5005-O PLATE
51647	55	AL 5005-H12 SHEET
51648	54	AL 5005-H12 PLATE
51649	55	AL 5005-H14 SHEET
51650	55	AL 5005-H14 PLATE
51651	55	AL 5005-H16 SHEET
51652	55	AL 5005-H18 SHEET
51653	55	AL 5005-H32 SHEET
51654	55	AL 5005-H32 PLATE
51655	55	AL 5005-H34 SHEET
51656	55	AL 5005-H34 PLATE
51657	55	AL 5005-H36 SHEET
51658	55	AL 5005-H38 SHEET
51659	54	AL 5005-H112 PLATE
51660	55	AL 5005-O ROD ROLLED
51661	55	AL 5005-H19 WIRE
51662	56	AL 5005-O WIRE RIVET AND COLD HEADING
51663	55	AL 5005-O ROD RIVET AND COLD HEADING
51664	55	AL 5005-H32 WIRE RIVET AND COLD HEADING
51665	55	AL 5005-H32 ROD RIVET AND COLD HEADING
51666	56	AL 5005-O TUBE DRAWN
51667	97	AL 6070-T6 ROD EXTRUDED
51668	97	AL 6070-T62 ROD EXTRUDED
51669	97	AL 6070-T6 BAR EXTRUDED
51670	97	AL 6070-T62 BAR EXTRUDED
51671	97	AL 6070-T6 SHAPES EXTRUDED
51672	97	AL 6070-T62 SHAPES EXTRUDED
51673	97	AL 6070-T6 TUBE EXTRUDED
51674	97	AL 6070-T62 TUBE EXTRUDED
51675	97	AL 6070 IMPACTS
51676	97	AL 6070-T6 PIPE
51677	97	AL 6070-T62 PIPE
51678	71	AL 5252-H24 SHEET
51679	71	AL 5252-H25 SHEET
51680	71	AL 5252-H28 SHEET
51681	42	AL 2319-F WIRE WELDING
51682	42	AL 2319-F ROD WELDING
51683	42	AL 2319-T351 ELECTRODES WELDING
51684	53	AL 4043-F ROD WELDING
51685	54	AL 4043-F WIRE WELDING
51686	54	AL 4043-T6 ELECTRODES WELDING
51687	53	AL 4043 WIRE SPRAY GUN
51688	54	AL 4043-T651 ELECTRODES WELDING
51689	100	AL 6201-T81 WIRE
51690	100	AL 6201-T81 CONDUCTOR
51691	79	AL 6053-T61 WIRE RIVET AND COLD HEADING
51692	79	AL 6053-T61 ROD RIVET AND COLD HEADING
51693	79	AL 6053-O WIRE RIVET AND COLD HEADING
51694	79	AL 6053-O ROD RIVET AND COLD HEADING
51695	78	AL 6053-H13 WIRE RIVET AND COLD HEADING
51696	78	AL 6053-H13 ROD RIVET AND COLD HEADING
51697	78	AL 6053-H23 WIRE RIVET AND COLD HEADING
51698	78	AL 6053-H23 ROD RIVET AND COLD HEADING
51699	9	AL 1145-O FOIL
51700	8	AL 1145-H19 FOIL
51701	76	AL 5457-O SHEET
51702	51	AL 3105-O SHEET
51703	51	AL 3105-H12 SHEET
51704	51	AL 3105-H14 SHEET
51705	51	AL 3105-H16 SHEET
51706	51	AL 3105-H18 SHEET
51707	51	AL 3105-H25 SHEET
51708	51	AL 3005-O SHEET
51709	51	AL 3005-H12 SHEET
51710	51	AL 3005-H14 SHEET
51711	51	AL 3005-H16 SHEET
51712	51	AL 3005-H18 SHEET
51713	51	AL 3005-H19 SHEET
51714	51	AL 3005-H26 SHEET
51715	51	AL 3005-H28 SHEET
51717	77	AL 5652-H32 SHEET

MSFC-HDBK-527 REV F 9999942 0005094 3

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
51718	77	AL 5652-H34 SHEET
51719	77	AL 5652-H36 SHEET
51720	77	AL 5652-H38 SHEET
51721	77	AL 5652-O PLATE
51722	77	AL 5652-H32 PLATE
51723	77	AL 5652-H34 PLATE
51724	77	AL 5652-H112 PLATE
51725	77	AL 5652-O TUBE EXTRUDED SEAMLESS
51726	77	AL 5652-H112 TUBE EXTRUDED SEAMLESS
51727	72	AL 5254-O SHEET
51728	72	AL 5254-O PLATE
51729	72	AL 5254-H32 SHEET
51730	72	AL 5254-H32 PLATE
51731	72	AL 5254-H34 SHEET
51732	72	AL 5254-H34 PLATE
51733	72	AL 5254-H36 SHEET
51734	72	AL 5254-H38 SHEET
51735	71	AL 5254-H112 PLATE
51736	72	AL 5254-O TUBE EXTRUDED SEAMLESS
51737	72	AL 5254-H112 TUBE EXTRUDED SEAMLESS
51738	78	AL 6005-T1 WIRE EXTRUDED
51739	78	AL 6005-T5 WIRE EXTRUDED
51740	78	AL 6005-T1 ROD EXTRUDED
51741	78	AL 6005-T5 ROD EXTRUDED
51742	78	AL 6005-T1 BAR EXTRUDED
51743	78	AL 6005-T5 BAR EXTRUDED
51744	78	AL 6005-T1 SHAPES EXTRUDED
51745	78	AL 6005-T5 SHAPES EXTRUDED
51746	78	AL 6005-T1 TUBE EXTRUDED
51747	78	AL 6005-T5 TUBE EXTRUDED
51748	77	AL 5657-H241 SHEET
51749	77	AL 5657-H25 SHEET
51750	77	AL 5657-H26 SHEET
51751	78	AL 5657-H28 SHEET
51752	50	AL 3004-O SHEET CLAD
51753	49	AL 3004-H32 SHEET CLAD
51754	49	AL 3004-H34 SHEET CLAD
51755	50	AL 3004-H36 SHEET CLAD
51756	50	AL 3004-H38 SHEET CLAD
51757	50	AL 3004-O PLATE CLAD
51758	49	AL 3004-H32 PLATE CLAD
51759	49	AL 3004-H34 PLATE CLAD
51760	49	AL 3004-H112 PLATE CLAD
51761	50	AL 3004-O TUBE WELDED CLAD
51762	49	AL 3004-H32 TUBE WELDED CLAD
51763	49	AL 3004-H34 TUBE WELDED CLAD
51764	50	AL 3004-H36 TUBE WELDED CLAD
51765	50	AL 3004-H38 TUBE WELDED CLAD
51766	36	AL 2117-O WIRE RIVET AND COLD HEADING
51767	36	AL 2117-O ROD RIVET AND COLD HEADING
51768	36	AL 2117-H15 WIRE RIVET AND COLD HEADING
51769	36	AL 2117-H15 ROD RIVET AND COLD HEADING
51770	36	AL 2117-H25 WIRE RIVET AND COLD HEADING
51771	36	AL 2117-H25 ROD RIVET AND COLD HEADING
51772	36	AL 2117-H23 ROD RIVET AND COLD HEADING
51773	97	AL 6101-T6 CONDUCTOR
51774	97	AL 6101-T61 CONDUCTOR
51775	97	AL 6101-T63 CONDUCTOR
51776	98	AL 6101-T64 CONDUCTOR
51777	98	AL 6101-T65 CONDUCTOR
51778	97	AL 6101-H111 CONDUCTOR
51779	103	AL 6351-T54 WIRE EXTRUDED
51780	102	AL 6351-T54 ROD EXTRUDED
51781	102	AL 6351-T54 BAR EXTRUDED
51782	103	AL 6351-T54 SHAPES EXTRUDED
51783	103	AL 6351-T54 TUBE EXTRUDED
51784	102	AL 6351-T5 PIPE
51785	103	AL 6351-T6 PIPE
51786	106	AL 7049-T73 FORGING HAND
51787	106	AL 7049-T7352 FORGING HAND
51788	106	AL 7049-T73 FORGING DIE
51789	106	AL 7049-T73510 EXTRUSIONS
51790	106	AL 7049-T73511 EXTRUSIONS
51791	106	AL 7049-T76510 EXTRUSIONS
51792	106	AL 7049-T76511 EXTRUSIONS
51793	106	AL 7049-T7351 PLATE
51794	57	AL 5050-O SHEET
51795	56	AL 5050-H32 SHEET
51796	56	AL 5050-H34 SHEET
51797	56	AL 5050-H36 SHEET
51798	57	AL 5050-H38 SHEET
51799	57	AL 5050-O PLATE
51800	56	AL 5050-H112 PLATE
51801	57	AL 5050-O TUBE DRAWN
51802	56	AL 5050-H32 TUBE DRAWN
51803	56	AL 5050-H34 TUBE DRAWN
51804	56	AL 5050-H36 TUBE DRAWN
51805	57	AL 5050-H38 TUBE DRAWN
51806	57	AL 5050-O TUBE WELDED
51807	56	AL 5050-H32 TUBE WELDED
51808	56	AL 5050-H34 TUBE WELDED
51809	56	AL 5050-H36 TUBE WELDED
51810	57	AL 5050-H38 TUBE WELDED
51811	42	AL 2319 ROD WELDING
51812	42	AL 2319 ELECTRODES WELDING
51813	53	AL 4043 ROD WELDING
51814	53	AL 4043 ELECTRODES WELDING
51815	77	AL 5654-O ELECTRODES WELDING
51816	77	AL 5654 ELECTRODES WELDING
51817	77	AL 5654 WIRE WELDING
51818	76	AL 5554 ROD WELDING
51819	76	AL 5554 ELECTRODES WELDING
51820	76	AL 5554-O ELECTRODES WELDING
51821	71	AL 5183 ROD WELDING
51822	71	AL 5183-O ELECTRODES WELDING
51823	54	AL 4145 METAL BRAZING FILLER
51824	54	AL 4145 ROD WELDING
51825	54	AL 4145-O ELECTRODES WELDING
51826	53	AL 4032-T6 FORGING DIE
51827	9	AL 1235-H111 TUBE EXTRUDED ROUND

MSFC-HDBK-527 REV F ■ 9999942 0005095 5 ■

Information Handling Services, 2000

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
51828	9	AL 1235-H112 TUBE EXTRUDED ROUND
51829	76	AL 5556 ROD WELDING
51830	76	AL 5556 ELECTRODES WELDING
51831	76	AL 5556-O ELECTRODES WELDING
51832	54	AL 4047 METAL BRAZING FILLER
51833	54	AL 4047 ROD WELDING
51834	54	AL 4047-T651 ELECTRODES WELDING
51835	54	AL 4047 ELECTRODES WELDING
51836	72	AL 5356 ROD WELDING
51837	72	AL 5356-O ELECTRODES WELDING
51839	94	AL 6066-O WIRE EXTRUDED
51840	94	AL 6066-T4 WIRE EXTRUDED
51841	95	AL 6066-T4510 WIRE EXTRUDED
51842	95	AL 6066-T4511 WIRE EXTRUDED
51843	95	AL 6066-T42 WIRE EXTRUDED
51844	96	AL 6066-T6 WIRE EXTRUDED
51845	96	AL 6066-T6510 WIRE EXTRUDED
51846	97	AL 6066-T6511 WIRE EXTRUDED
51847	96	AL 6066-T62 WIRE EXTRUDED
51848	94	AL 6066-O ROD EXTRUDED
51849	94	AL 6066-T4 ROD EXTRUDED
51850	95	AL 6066-T4510 ROD EXTRUDED
51851	95	AL 6066-T4511 ROD EXTRUDED
51852	95	AL 6066-T42 ROD EXTRUDED
51853	95	AL 6066-T6 ROD EXTRUDED
51854	96	AL 6066-T6510 ROD EXTRUDED
51855	96	AL 6066-T6511 ROD EXTRUDED
51856	96	AL 6066-T62 ROD EXTRUDED
51857	94	AL 6066-O BAR EXTRUDED
51858	94	AL 6066-T4 BAR EXTRUDED
51859	95	AL 6066-T4510 BAR EXTRUDED
51860	95	AL 6066-T4511 BAR EXTRUDED
51861	94	AL 6066-T42 BAR EXTRUDED
51862	95	AL 6066-T6 BAR EXTRUDED
51863	96	AL 6066-T6510 BAR EXTRUDED
51864	96	AL 6066-T6511 BAR EXTRUDED
51865	96	AL 6066-T62 BAR EXTRUDED
51866	94	AL 6066-O SHAPES EXTRUDED
51867	94	AL 6066-T4 SHAPES EXTRUDED
51868	95	AL 6066-T4510 SHAPES EXTRUDED
51869	95	AL 6066-T4511 SHAPES EXTRUDED
51870	95	AL 6066-T42 SHAPES EXTRUDED
51871	96	AL 6066-T6 SHAPES EXTRUDED
51872	96	AL 6066-T6510 SHAPES EXTRUDED
51873	96	AL 6066-T6511 SHAPES EXTRUDED
51874	96	AL 6066-T62 SHAPES EXTRUDED
51875	94	AL 6066-O TUBE EXTRUDED
51876	94	AL 6066-T4 TUBE EXTRUDED
51877	95	AL 6066-T4510 TUBE EXTRUDED
51878	95	AL 6066-T4511 TUBE EXTRUDED
51879	95	AL 6066-T42 TUBE EXTRUDED
51880	96	AL 6066-T6 TUBE EXTRUDED
51881	96	AL 6066-T6510 TUBE EXTRUDED
51882	96	AL 6066-T6511 TUBE EXTRUDED
51883	96	AL 6066-T62 TUBE EXTRUDED
51884	95	AL 6066-T6 FORGING DIE
51885	74	AL 5454-O SHEET
51886	74	AL 5454-O PLATE
51887	73	AL 5454-H32 SHEET
51888	73	AL 5454-H32 PLATE
51889	73	AL 5454-H34 SHEET
51890	73	AL 5454-H34 PLATE
51891	73	AL 5454-H112 PLATE
51892	74	AL 5454-O WIRE EXTRUDED
51893	74	AL 5454-O ROD EXTRUDED
51894	74	AL 5454-O BAR EXTRUDED
51895	74	AL 5454-O SHAPES EXTRUDED
51896	74	AL 5454-O TUBE EXTRUDED
51897	73	AL 5454-H111 WIRE EXTRUDED
51898	72	AL 5454-H111 ROD EXTRUDED
51899	72	AL 5454-H111 BAR EXTRUDED
51900	72	AL 5454-H111 SHAPES EXTRUDED
51901	73	AL 5454-H111 TUBE EXTRUDED
51902	73	AL 5454-H112 WIRE EXTRUDED
51903	73	AL 5454-H112 ROD EXTRUDED
51904	73	AL 5454-H112 BAR EXTRUDED
51905	73	AL 5454-H112 SHAPES EXTRUDED
51906	73	AL 5454-H112 TUBE EXTRUDED
51907	74	AL 5454-O TUBE WELDED
51908	73	AL 5454-H32 TUBE WELDED
51909	74	AL 5454-H34 TUBE WELDED
51910	73	AL 5454-H112 TUBE WELDED
51911	63	AL 5052-O WIRE ROLLED
51912	62	AL 5052-O ROD ROLLED
51913	61	AL 5052-O BAR ROLLED
51914	59	AL 5052-H32 WIRE ROLLED
51915	60	AL 5052-H34 WIRE ROLLED
51916	61	AL 5052-H36 WIRE ROLLED
51917	61	AL 5052-H38 WIRE ROLLED
51918	58	AL 5052-F ROD ROLLED
51919	58	AL 5052-F BAR ROLLED
51920	58	AL 5052-F WIRE ROLLED
51921	60	AL 5052-H36 ROD DRAWN
51922	61	AL 5052-H38 ROD DRAWN
51923	62	AL 5052-O WIRE DRAWN
51924	59	AL 5052-H32 WIRE DRAWN
51925	60	AL 5052-H34 WIRE DRAWN
51926	61	AL 5052-H36 WIRE DRAWN
51927	61	AL 5052-H38 WIRE DRAWN
51928	62	AL 5052-O ROD DRAWN
51929	59	AL 5052-H32 ROD DRAWN
51930	59	AL 5052-H34 ROD DRAWN
51931	61	AL 5052-O BAR DRAWN
51932	58	AL 5052-H32 BAR DRAWN
51933	59	AL 5052-H34 BAR DRAWN
51934	60	AL 5052-H36 BAR DRAWN
51935	61	AL 5052-H38 BAR DRAWN
51936	62	AL 5052-O TUBE DRAWN
51937	59	AL 5052-H32 TUBE DRAWN
51938	60	AL 5052-H34 TUBE DRAWN

MSFC-HDBK-527 REV F ■ 9999942 0005096 7 ■

MATCD	PAGE	DESIGNATION
51939	60	AL 5052-H36 TUBE DRAWN
51940	61	AL 5052-H38 TUBE DRAWN
51941	62	AL 5052-O TUBE EXTRUDED
51942	59	AL 5052-H32 TUBE CONDENSER
51943	60	AL 5052-H34 TUBE CONDENSER
51944	62	AL 5052-O TUBE WELDED
51945	60	AL 5052-H36 TUBE WELDED
51946	61	AL 5052-H38 TUBE WELDED
51947	58	AL 5052-H112 TUBE ROUND
51948	62	AL 5052-O WIRE RIVET AND COLD HEADING
51949	59	AL 5052-H32 WIRE RIVET AND COLD HEADING
51950	62	AL 5052-O ROD RIVET AND COLD HEADING
51951	59	AL 5052-H32 ROD RIVET AND COLD HEADING
51952	58	AL 5052-H22 WIRE RIVET
51953	58	AL 5052-H22 ROD RIVET
51954	61	AL 5052-O FOIL
51955	58	AL 5052-H19 FOIL
51956	58	AL 5052-H112 PLATE
51957	5	AL 1100-H12 SHEET
51958	5	AL 1100-H12 PLATE
51959	6	AL 1100-H16 SHEET
51960	7	AL 1100-H18 SHEET
51961	4	AL 1100-H112 PLATE
51962	8	AL 1100-O WIRE ROLLED
51963	8	AL 1100-O ROD ROLLED
51964	7	AL 1100-O BAR ROLLED
51965	6	AL 1100-H12 WIRE ROLLED
51966	6	AL 1100-H14 WIRE ROLLED
51967	7	AL 1100-H16 WIRE ROLLED
51968	7	AL 1100-H18 WIRE ROLLED
51969	5	AL 1100-H112 WIRE ROLLED
51970	5	AL 1100-H112 ROD ROLLED
51971	4	AL 1100-H112 BAR ROLLED
51972	4	AL 1100-F WIRE ROLLED
51973	4	AL 1100-F ROD ROLLED
51974	4	AL 1100-F BAR ROLLED
51975	7	AL 1100-O BAR EXTRUDED
51976	4	AL 1100-H112 BAR EXTRUDED
51977	8	AL 1100-O ROD EXTRUDED
51978	5	AL 1100-H112 ROD EXTRUDED
51979	8	AL 1100-O WIRE EXTRUDED
51980	5	AL 1100-H112 WIRE EXTRUDED
51981	8	AL 1100-O SHAPES EXTRUDED
51982	5	AL 1100-H112 SHAPES EXTRUDED
51983	8	AL 1100-O TUBE EXTRUDED
51984	5	AL 1100-H112 TUBE EXTRUDED
51985	5	AL 1100-H12 TUBE DRAWN
51986	6	AL 1100-H14 TUBE DRAWN
51987	6	AL 1100-H16 TUBE DRAWN
51988	7	AL 1100-H18 TUBE DRAWN
51989	5	AL 1100-H113 TUBE DRAWN
51990	6	AL 1100-H14 TUBE DRAWN SEAMLESS
51991	8	AL 1100-O TUBE WELDED
51992	6	AL 1100-H12 TUBE WELDED
51993	6	AL 1100-H14 TUBE WELDED
51994	6	AL 1100-H16 TUBE WELDED
51996	7	AL 1100-H18 TUBE WELDED
51997	8	AL 1100-O WIRE RIVET AND COLD HEADING
51998	6	AL 1100-H14 WIRE RIVET AND COLD HEADING
51999	8	AL 1100-O ROD RIVET AND COLD HEADING
52000	6	AL 1100-H14 ROD RIVET AND COLD HEADING
52001	7	AL 1100-H24 WIRE RIVET AND COLD HEADING
52002	7	AL 1100-H24 ROD RIVET AND COLD HEADING
52003	4	AL 1100-H112 FORGING DIE
52004	7	AL 1100-O FOIL
52005	7	AL 1100-H19 FOIL
52006	9	AL 2011-T3 TUBE DRAWN SEAMLESS
52007	10	AL 2011-T4511 TUBE DRAWN SEAMLESS
52008	11	AL 2011-T8 TUBE DRAWN SEAMLESS
52009	9	AL 2011-T3 ROD ROLLED
52010	10	AL 2011-T4 ROD ROLLED
52011	10	AL 2011-T451 ROD ROLLED
52012	11	AL 2011-T8 ROD ROLLED
52013	9	AL 2011-T3 BAR ROLLED
52014	10	AL 2011-T4 BAR ROLLED
52015	10	AL 2011-T451 BAR ROLLED
52016	11	AL 2011-T8 BAR ROLLED
52017	10	AL 2011-T3 WIRE ROLLED
52018	11	AL 2011-T8 WIRE ROLLED
52028	71	AL 5154-O ROD ROLLED
52029	69	AL 5154-H112 ROD ROLLED
52030	70	AL 5154-O BAR ROLLED
52031	68	AL 5154-H112 BAR ROLLED
52032	71	AL 5154-O WIRE ROLLED
52033	69	AL 5154-H112 WIRE ROLLED
52034	69	AL 5154-H32 WIRE ROLLED
52035	70	AL 5154-H34 WIRE ROLLED
52036	70	AL 5154-H36 WIRE ROLLED
52037	70	AL 5154-H38 WIRE ROLLED
52038	71	AL 5154-O WIRE EXTRUDED
52039	69	AL 5154-H112 WIRE EXTRUDED
52040	70	AL 5154-O ROD EXTRUDED
52041	69	AL 5154-H112 ROD EXTRUDED
52042	70	AL 5154-O BAR EXTRUDED
52043	68	AL 5154-H112 BAR EXTRUDED
52044	71	AL 5154-O SHAPES EXTRUDED
52045	69	AL 5154-H112 SHAPES EXTRUDED
52046	71	AL 5154-O TUBE EXTRUDED
52047	69	AL 5154-H112 TUBE EXTRUDED
52048	71	AL 5154-O TUBE DRAWN SEAMLESS
52049	69	AL 5154-H34 TUBE DRAWN SEAMLESS
52050	70	AL 5154-H38 TUBE DRAWN SEAMLESS
52051	71	AL 5154-O TUBE WELDED
52052	69	AL 5154-H32 TUBE WELDED
52053	69	AL 5154-H34 TUBE WELDED
52054	70	AL 5154-H36 TUBE WELDED
52055	70	AL 5154-H38 TUBE WELDED
52056	3	AL 1060-O SHEET
52057	1	AL 1060-H12 SHEET
52058	2	AL 1060-H14 SHEET

MSFC-HDBK-527 REV F 9999942 0005097 9

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
52059	2	AL 1060-H16 SHEET
52060	2	AL 1060-H18 SHEET
52061	1	AL 1060-H112 SHEET
52062	3	AL 1060-O PLATE
52063	1	AL 1060-H12 PLATE
52064	1	AL 1060-H14 PLATE
52065	1	AL 1060-H112 PLATE
52067	4	AL 1060-O WIRE ROLLED
52068	2	AL 1060-H14 WIRE ROLLED
52069	2	AL 1060-H18 WIRE ROLLED
52070	3	AL 1060-O ROD ROLLED
52071	2	AL 1060-H14 ROD ROLLED
52072	2	AL 1060-H18 ROD ROLLED
52073	3	AL 1060-O BAR ROLLED
52074	1	AL 1060-H14 BAR ROLLED
52075	2	AL 1060-H18 BAR ROLLED
52076	3	AL 1060-O TUBE EXTRUDED
52077	1	AL 1060-H112 TUBE EXTRUDED
52078	3	AL 1060-O SHAPES EXTRUDED
52079	1	AL 1060-H112 SHAPES EXTRUDED
52080	3	AL 1060-O BAR EXTRUDED
52081	1	AL 1060-H112 BAR EXTRUDED
52082	3	AL 1060-O ROD EXTRUDED
52083	1	AL 1060-H112 ROD EXTRUDED
52084	3	AL 1060-O WIRE EXTRUDED
52085	1	AL 1060-H112 WIRE EXTRUDED
52086	3	AL 1060-O TUBE DRAWN
52087	1	AL 1060-H12 TUBE DRAWN
52088	2	AL 1060-H14 TUBE DRAWN
52089	2	AL 1060-H18 TUBE DRAWN
52090	1	AL 1060-H113 TUBE DRAWN
52091	2	AL 1060-H14 TUBE CONDENSER
52092	3	AL 1060-O TUBE CONDENSER
52094	98	AL 6162-T5 WIRE EXTRUDED
52095	98	AL 6162-T5 ROD EXTRUDED
52096	98	AL 6162-T5 BAR EXTRUDED
52097	98	AL 6162-T5 SHAPES EXTRUDED
52098	98	AL 6162-T5 TUBE EXTRUDED
52099	98	AL 6162-T5510 WIRE EXTRUDED
52100	98	AL 6162-T5510 ROD EXTRUDED
52101	98	AL 6162-T5510 BAR EXTRUDED
52102	98	AL 6162-T5510 SHAPES EXTRUDED
52103	98	AL 6162-T5510 TUBE EXTRUDED
52104	99	AL 6162-T5511 WIRE EXTRUDED
52105	99	AL 6162-T5511 ROD EXTRUDED
52106	98	AL 6162-T5511 BAR EXTRUDED
52107	99	AL 6162-T5511 SHAPES EXTRUDED
52108	99	AL 6162-T5511 TUBE EXTRUDED
52109	99	AL 6162-T6 WIRE EXTRUDED
52110	99	AL 6162-T6 ROD EXTRUDED
52111	99	AL 6162-T6 BAR EXTRUDED
52112	99	AL 6162-T6 SHAPES EXTRUDED
52113	99	AL 6162-T6 TUBE EXTRUDED
52114	99	AL 6162-T6510 WIRE EXTRUDED
52115	99	AL 6162-T6510 ROD EXTRUDED
52116	99	AL 6162-T6510 BAR EXTRUDED
52117	99	AL 6162-T6510 SHAPES EXTRUDED
52118	99	AL 6162-T6510 TUBE EXTRUDED
52119	100	AL 6162-T6511 WIRE EXTRUDED
52120	99	AL 6162-T6511 ROD EXTRUDED
52121	99	AL 6162-T6511 BAR EXTRUDED
52122	99	AL 6162-T6511 SHAPES EXTRUDED
52123	100	AL 6162-T6511 TUBE EXTRUDED
52124	90	AL 6063-O WIRE EXTRUDED
52125	90	AL 6063-O ROD EXTRUDED
52126	89	AL 6063-O BAR EXTRUDED
52127	90	AL 6063-O SHAPES EXTRUDED
52128	90	AL 6063-O TUBE EXTRUDED
52129	92	AL 6063-T5 WIRE EXTRUDED
52130	92	AL 6063-T5 ROD EXTRUDED
52131	92	AL 6063-T5 BAR EXTRUDED
52132	92	AL 6063-T5 SHAPES EXTRUDED
52133	92	AL 6063-T5 TUBE EXTRUDED
52134	90	AL 6063-O TUBE DRAWN
52135	92	AL 6063-T6 PIPE
52136	90	AL 6063-O PIPE
52138	93	AL 6063-T6 PIPE EXTRUDED STRUCTURAL
52139	92	AL 6063-T52 SHAPES EXTRUDED
52140	93	AL 6063-T6 WIRE EXTRUDED
52141	93	AL 6063-T6 ROD EXTRUDED
52143	93	AL 6063-T6 SHAPES EXTRUDED
52144	92	AL 6063-T52 TUBE EXTRUDED
52145	93	AL 6063-T6 TUBE EXTRUDED
52146	91	AL 6063-T4 TUBE DRAWN
52147	93	AL 6063-T6 TUBE DRAWN
52148	94	AL 6063-T83 TUBE DRAWN
52149	94	AL 6063-T831 TUBE DRAWN
52150	94	AL 6063-T832 TUBE DRAWN
52151	91	AL 6063-T42 TUBE DRAWN
52152	93	AL 6063-T62 TUBE DRAWN
52153	90	AL 6063-T1 WIRE EXTRUDED
52154	90	AL 6063-T1 ROD EXTRUDED
52155	90	AL 6063-T1 BAR EXTRUDED
52156	90	AL 6063-T1 SHAPES EXTRUDED
52157	90	AL 6063-T1 TUBE EXTRUDED
52158	91	AL 6063-T4 WIRE EXTRUDED
52159	91	AL 6063-T4 ROD EXTRUDED
52160	91	AL 6063-T4 BAR EXTRUDED
52161	91	AL 6063-T4 SHAPES EXTRUDED
52162	91	AL 6063-T4 TUBE EXTRUDED
52163	93	AL 6063-T62 TUBE EXTRUDED SEAMLESS
52164	90	AL 6063-T31 TUBE DRAWN SEAMLESS
52165	91	AL 6063-T42 SHAPES EXTRUDED
52166	91	AL 6063-T42 TUBE EXTRUDED
52167	90	AL 6063-T1 PIPE
52168	91	AL 6063-T4 PIPE
52169	91	AL 6063-T42 PIPE
52170	92	AL 6063-T5 PIPE
52171	92	AL 6063-T52 PIPE
52172	92	AL 6063-T6 PIPE

MSFC-HDBK-527 REV F ■ 9999942 0005098 0 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
52173	93	AL 6063-T62 PIPE
52174	122	AL 7178-O SHEET
52175	122	AL 7178-O PLATE
52176	123	AL 7178-T6 SHEET
52177	124	AL 7178-T62 SHEET
52178	124	AL 7178-T62 PLATE
52179	124	AL 7178-T651 PLATE
52180	125	AL 7178-T76 SHEET
52181	125	AL 7178-T7651 PLATE
52182	123	AL 7178-T6 PLATE
52183	123	AL 7178-O WIRE EXTRUDED
52184	122	AL 7178-O ROD EXTRUDED
52185	122	AL 7178-O BAR EXTRUDED
52186	122	AL 7178-O SHAPES EXTRUDED
52187	123	AL 7178-O TUBE EXTRUDED
52188	123	AL 7178-T6 WIRE EXTRUDED
52189	123	AL 7178-T6 ROD EXTRUDED
52190	123	AL 7178-T6 BAR EXTRUDED
52191	123	AL 7178-T6 SHAPES EXTRUDED
52192	123	AL 7178-T6 TUBE EXTRUDED
52193	125	AL 7178-T6510 WIRE EXTRUDED
52194	124	AL 7178-T6510 ROD EXTRUDED
52195	124	AL 7178-T6510 BAR EXTRUDED
52196	124	AL 7178-T6510 SHAPES EXTRUDED
52197	125	AL 7178-T6510 TUBE EXTRUDED
52198	125	AL 7178-T6511 WIRE EXTRUDED
52199	125	AL 7178-T6511 ROD EXTRUDED
52200	125	AL 7178-T6511 BAR EXTRUDED
52201	125	AL 7178-T6511 SHAPES EXTRUDED
52202	125	AL 7178-T6511 TUBE EXTRUDED
52203	124	AL 7178-T62 WIRE EXTRUDED
52204	124	AL 7178-T62 ROD EXTRUDED
52205	124	AL 7178-T62 BAR EXTRUDED
52206	124	AL 7178-T62 SHAPES EXTRUDED
52207	124	AL 7178-T62 TUBE EXTRUDED
52208	125	AL 7178-T76 WIRE EXTRUDED
52209	125	AL 7178-T76 ROD EXTRUDED
52210	125	AL 7178-T76 BAR EXTRUDED
52211	125	AL 7178-T76 SHAPES EXTRUDED
52212	125	AL 7178-T76 TUBE EXTRUDED
52213	126	AL 7178-T76510 WIRE EXTRUDED
52214	126	AL 7178-T76510 ROD EXTRUDED
52215	126	AL 7178-T76510 BAR EXTRUDED
52216	126	AL 7178-T76510 SHAPES EXTRUDED
52217	126	AL 7178-T76510 TUBE EXTRUDED
52218	126	AL 7178-T76511 WIRE EXTRUDED
52219	126	AL 7178-T76511 ROD EXTRUDED
52220	126	AL 7178-T76511 BAR EXTRUDED
52221	126	AL 7178-T76511 SHAPES EXTRUDED
52222	126	AL 7178-T76511 TUBE EXTRUDED
52223	123	AL 7178-O WIRE RIVET AND COLD HEADING
52224	122	AL 7178-H13 WIRE RIVET AND COLD HEADING
52225	123	AL 7178-T6 WIRE RIVET AND COLD HEADING
52226	122	AL 7178-O ROD RIVET AND COLD HEADING
52227	122	AL 7178-H13 ROD RIVET AND COLD HEADING
52228	123	AL 7178-T6 ROD RIVET AND COLD HEADING
52229	101	AL 6262-T6 WIRE ROLLED
52230	100	AL 6262-T6 ROD ROLLED
52231	100	AL 6262-T6 BAR ROLLED
52232	101	AL 6262-T651 WIRE ROLLED
52233	101	AL 6262-T651 ROD ROLLED
52234	101	AL 6262-T651 BAR ROLLED
52235	102	AL 6262-T9 WIRE ROLLED
52236	102	AL 6262-T9 ROD ROLLED
52237	102	AL 6262-T9 BAR ROLLED
52238	101	AL 6262-T6 WIRE EXTRUDED
52239	100	AL 6262-T6 ROD EXTRUDED
52240	100	AL 6262-T6 BAR EXTRUDED
52241	100	AL 6262-T6 SHAPES EXTRUDED
52242	101	AL 6262-T6 TUBE EXTRUDED
52243	101	AL 6262-T6510 WIRE EXTRUDED
52244	101	AL 6262-T6510 ROD EXTRUDED
52245	101	AL 6262-T6510 BAR EXTRUDED
52246	100	AL 6262-T6 TUBE DRAWN
52247	101	AL 6262-T62 TUBE DRAWN
52248	102	AL 6262-T9 TUBE DRAWN
52249	101	AL 6262-T6510 SHAPES EXTRUDED
52250	101	AL 6262-T6510 TUBE EXTRUDED
52251	102	AL 6262-T6511 WIRE EXTRUDED
52252	102	AL 6262-T6511 ROD EXTRUDED
52253	102	AL 6262-T6511 BAR EXTRUDED
52254	102	AL 6262-T6511 SHAPES EXTRUDED
52255	102	AL 6262-T6511 TUBE EXTRUDED
52270	76	AL 5456-O PLATE
52271	75	AL 5456-H116 PLATE
52272	76	AL 5456-O SHEET
52273	75	AL 5456-H116 SHEET
52274	76	AL 5456-O BAR EXTRUDED
52275	76	AL 5456-O ROD EXTRUDED
52276	76	AL 5456-O SHAPES EXTRUDED
52277	74	AL 5456-H111 SHAPES EXTRUDED
52278	75	AL 5456-H112 SHAPES EXTRUDED
52279	76	AL 5456-O TUBE EXTRUDED
52280	74	AL 5456-H111 TUBE EXTRUDED
52281	75	AL 5456-H112 TUBE EXTRUDED
52282	76	AL 5456-O WIRE EXTRUDED
52283	76	AL 5456-O TUBE EXTRUDED SEAMLESS
52284	74	AL 5456-H111 TUBE EXTRUDED SEAMLESS
52285	75	AL 5456-H112 TUBE EXTRUDED SEAMLESS
52286	76	AL 5456-O TUBE DRAWN SEAMLESS
52287	107	AL 7050-T7651 PLATE
52288	107	AL 7050-T7451 PLATE
52289	107	AL 7050-T76511 WIRE EXTRUDED
52290	107	AL 7050-T76511 ROD EXTRUDED
52291	107	AL 7050-T76511 BAR EXTRUDED
52292	107	AL 7050-T73511 WIRE EXTRUDED
52293	107	AL 7050-T73511 ROD EXTRUDED
52294	107	AL 7050-T73511 BAR EXTRUDED
52295	107	AL 7050-T74511 WIRE EXTRUDED
52296	107	AL 7050-T74511 ROD EXTRUDED

MSFC-HDBK-527 REV F 9999942 0005099 2

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
52297	107	AL 7050-T74511 BAR EXTRUDED
52298	107	AL 7050-T7452 FORGING HAND
52299	107	AL 7050-T74 FORGING DIE
52300	106	AL 7050-O WIRE RIVET AND COLD HEADING
52301	106	AL 7050-H13 WIRE RIVET AND COLD HEADING
52302	106	AL 7050-O ROD RIVET AND COLD HEADING
52303	106	AL 7050-H13 ROD RIVET AND COLD HEADING
52304	107	AL 7050-T7 WIRE RIVET AND COLD HEADING
52305	106	AL 7050-T7 ROD RIVET AND COLD HEADING
52306	12	AL 2014-O ROD ROLLED
52307	13	AL 2014-T4 ROD ROLLED
52308	14	AL 2014-T42 ROD ROLLED
52309	15	AL 2014-T451 ROD ROLLED
52310	17	AL 2014-T6 ROD ROLLED
52311	19	AL 2014-T62 ROD ROLLED
52312	20	AL 2014-T651 ROD ROLLED
52313	12	AL 2014-O ROD COLD FINISHED
52314	13	AL 2014-T4 ROD COLD FINISHED
52315	14	AL 2014-T42 ROD COLD FINISHED
52316	15	AL 2014-T451 ROD COLD FINISHED
52317	17	AL 2014-T6 ROD COLD FINISHED
52318	18	AL 2014-T62 ROD COLD FINISHED
52319	20	AL 2014-T651 ROD COLD FINISHED
52320	12	AL 2014-O WIRE ROLLED
52321	14	AL 2014-T4 WIRE ROLLED
52322	15	AL 2014-T42 WIRE ROLLED
52323	16	AL 2014-T451 WIRE ROLLED
52324	18	AL 2014-T6 WIRE ROLLED
52325	19	AL 2014-T62 WIRE ROLLED
52326	20	AL 2014-T651 WIRE ROLLED
52327	12	AL 2014-O WIRE COLD FINISHED
52328	14	AL 2014-T4 WIRE COLD FINISHED
52329	15	AL 2014-T42 WIRE COLD FINISHED
52330	15	AL 2014-T451 WIRE COLD FINISHED
52331	18	AL 2014-T6 WIRE COLD FINISHED
52332	19	AL 2014-T62 WIRE COLD FINISHED
52333	20	AL 2014-T651 WIRE COLD FINISHED
52334	11	AL 2014-O BAR DRAWN
52335	13	AL 2014-T4 BAR DRAWN
52336	14	AL 2014-T42 BAR DRAWN
52337	15	AL 2014-T451 BAR DRAWN
52338	16	AL 2014-T6 BAR DRAWN
52339	18	AL 2014-T62 BAR DRAWN
52340	19	AL 2014-T651 BAR DRAWN
52341	12	AL 2014-O ROD DRAWN
52342	13	AL 2014-T4 ROD DRAWN
52343	14	AL 2014-T42 ROD DRAWN
52344	15	AL 2014-T451 ROD DRAWN
52345	17	AL 2014-T6 ROD DRAWN
52346	18	AL 2014-T62 ROD DRAWN
52347	20	AL 2014-T651 ROD DRAWN
52348	12	AL 2014-O WIRE DRAWN
52349	18	AL 2014-T6 WIRE DRAWN
52350	15	AL 2014-T42 WIRE DRAWN
52351	16	AL 2014-T451 WIRE DRAWN
52353	19	AL 2014-T62 WIRE DRAWN
52354	20	AL 2014-T651 WIRE DRAWN
52355	11	AL 2014-O BAR EXTRUDED
52356	13	AL 2014-T4 BAR EXTRUDED
52357	16	AL 2014-T4510 BAR EXTRUDED
52358	16	AL 2014-T4511 BAR EXTRUDED
52359	14	AL 2014-T42 BAR EXTRUDED
52360	17	AL 2014-T6 BAR EXTRUDED
52361	20	AL 2014-T6510 BAR EXTRUDED
52362	20	AL 2014-T6511 BAR EXTRUDED
52363	18	AL 2014-T62 BAR EXTRUDED
52364	12	AL 2014-O ROD EXTRUDED
52365	13	AL 2014-T4 ROD EXTRUDED
52366	16	AL 2014-T4510 ROD EXTRUDED
52367	16	AL 2014-T4511 ROD EXTRUDED
52368	14	AL 2014-T42 ROD EXTRUDED
52369	17	AL 2014-T6 ROD EXTRUDED
52370	20	AL 2014-T6510 ROD EXTRUDED
52371	20	AL 2014-T6511 ROD EXTRUDED
52372	19	AL 2014-T62 ROD EXTRUDED
52373	12	AL 2014-O SHAPES EXTRUDED
52374	13	AL 2014-T4 SHAPES EXTRUDED
52375	16	AL 2014-T4510 SHAPES EXTRUDED
52376	16	AL 2014-T4511 SHAPES EXTRUDED
52377	14	AL 2014-T42 SHAPES EXTRUDED
52378	17	AL 2014-T6 SHAPES EXTRUDED
52379	20	AL 2014-T6510 SHAPES EXTRUDED
52380	20	AL 2014-T6511 SHAPES EXTRUDED
52381	19	AL 2014-T62 SHAPES EXTRUDED
52382	12	AL 2014-O TUBE EXTRUDED
52383	13	AL 2014-T4 TUBE EXTRUDED
52384	16	AL 2014-T4510 TUBE EXTRUDED
52385	16	AL 2014-T4511 TUBE EXTRUDED
52386	15	AL 2014-T42 TUBE EXTRUDED
52387	18	AL 2014-T6 TUBE EXTRUDED
52388	20	AL 2014-T6510 TUBE EXTRUDED
52389	20	AL 2014-T6511 TUBE EXTRUDED
52390	19	AL 2014-T62 TUBE EXTRUDED
52391	12	AL 2014-O WIRE EXTRUDED
52392	14	AL 2014-T4 WIRE EXTRUDED
52393	16	AL 2014-T4510 WIRE EXTRUDED
52394	16	AL 2014-T4511 WIRE EXTRUDED
52395	15	AL 2014-T42 WIRE EXTRUDED
52396	18	AL 2014-T6 WIRE EXTRUDED
52397	20	AL 2014-T6510 WIRE EXTRUDED
52398	21	AL 2014-T6511 WIRE EXTRUDED
52399	19	AL 2014-T62 WIRE EXTRUDED
52400	12	AL 2014-O TUBE EXTRUDED SEAMLESS
52401	14	AL 2014-T4 TUBE EXTRUDED SEAMLESS
52402	16	AL 2014-T4510 TUBE EXTRUDED SEAMLESS
52403	16	AL 2014-T4511 TUBE EXTRUDED SEAMLESS
52404	15	AL 2014-T42 TUBE EXTRUDED SEAMLESS
52405	18	AL 2014-T6 TUBE EXTRUDED SEAMLESS
52406	20	AL 2014-T6510 TUBE EXTRUDED SEAMLESS
52407	20	AL 2014-T6511 TUBE EXTRUDED SEAMLESS

MSFC-HDBK-527 REV F 9999942 0005100 5

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
52408	19	AL 2014-T62 TUBE EXTRUDED SEAMLESS
52409	12	AL 2014-O TUBE DRAWN SEAMLESS
52410	13	AL 2014-T4 TUBE DRAWN SEAMLESS
52411	15	AL 2014-T42 TUBE DRAWN SEAMLESS
52412	18	AL 2014-T6 TUBE DRAWN SEAMLESS
52413	19	AL 2014-T62 TUBE DRAWN SEAMLESS
52414	17	AL 2014-T6 FORGING DIE
52415	13	AL 2014-T4 FORGING DIE
52416	17	AL 2014-T6 FORGING HAND
52417	21	AL 2014-T652 FORGING HAND
52418	17	AL 2014-T6 RINGS ROLLED
52419	21	AL 2014-T652 RINGS ROLLED
52420	17	AL 2014-T6 FORGING
52421	11	AL 2014 FORGING STOCK
52422	13	AL 2014-T4 FORGING
52423	11	AL 2014-O IMPACTS
52424	13	AL 2014-T4 IMPACTS
52425	17	AL 2014-T6 IMPACTS
52426	131	BERYLLIUM RODS
52427	131	BERYLLIUM SHAPES
52428	148	CRES 17PH-4MO H1075 RING
52429	152	CRES 19-9DL STRIP ANNEALED
52430	109	AL 7075-O SHEET CLAD
52431	113	AL 7075-T62 SHEET CLAD
52432	108	AL 7075-O PLATE CLAD
52433	112	AL 7075-T62 PLATE CLAD
52434	114	AL 7075-T651 PLATE CLAD
52435	114	AL 7075-T651 PLATE CLAD
52436	111	AL 7075-T6 PLATE CLAD
52437	164	CRES 420 PLATE
52438	164	CRES 420 SHEET
52439	164	CRES 420 STRIP
52440	164	CRES 430 SHAPES ANNEALED
52441	164	CRES 430 FORGING ANNEALED
52442	165	CRES 430 WIRE ANNEALED
52443	167	CRES 446 WIRE
52444	167	CRES 446 SHAPES
52445	167	CRES 446 FORGING
52446	167	CRES 446 SHEET
52447	167	CRES 446 STRIP
52448	109	AL 7075-O SHEET ONE SIDE CLAD
52449	112	AL 7075-T6 SHEET ONE SIDE CLAD
52450	113	AL 7075-T62 SHEET ONE SIDE CLAD
52451	109	AL 7075-O PLATE ONE SIDE CLAD
52452	113	AL 7075-T62 PLATE ONE SIDE CLAD
52453	114	AL 7075-T651 PLATE ONE SIDE CLAD
52454	111	AL 7075-T6 PLATE ONE SIDE CLAD
52455	24	AL 2024-O SHEET 1 1/2% CLAD
52456	24	AL 2024-O PLATE 1 1/2% CLAD
52457	23	AL 2024 SHEET ONE SIDE CLAD
52458	23	AL 2024 PLATE ONE SIDE CLAD
52459	24	AL 2024-O SHEET 1 1/2% ONE SIDE CLAD
52460	24	AL 2024-O PLATE 1 1/2% ONE SIDE CLAD
52461	109	AL 7075-O SHEET 2 1/2% CLAD
52462	108	AL 7075-O PLATE 1 1/2% CLAD
52463	109	AL 7075-O SHEET 2 1/2% ONE SIDE CLAD
52464	108	AL 7075-O PLATE 2 1/2% ONE SIDE CLAD
52465	109	AL 7075-O SHEET CLAD W/7011
52466	111	AL 7075-T6 SHEET CLAD W/7011
52467	113	AL 7075-T62 SHEET CLAD W/7011
52468	120	AL 7075-T76 SHEET CLAD W/7011
52469	108	AL 7075-O PLATE CLAD W/7011
52470	113	AL 7075-T62 PLATE CLAD W/7011
52471	114	AL 7075-T651 PLATE CLAD W/7011
52472	120	AL 7075-T7651 PLATE CLAD W/7011
52473	109	AL 7075-O SHEET CLAD W/7008
52474	108	AL 7075-O PLATE CLAD W/7008
52475	122	AL 7178-O SHEET CLAD
52476	122	AL 7178-O PLATE CLAD
52477	123	AL 7178-T6 PLATE CLAD
52478	124	AL 7178-T62 SHEET CLAD
52479	124	AL 7178-T62 PLATE CLAD
52480	124	AL 7178-T651 PPLATE CLAD
52481	125	AL 7178-T76 SHEET CLAD
52482	126	AL 7178-T7651 PLATE CLAD
52483	127	AL A140
52484	42	AL 2420-T77 SAND CASTING (WAS 142)
52485	127	AL A142
52486	43	AL 2950-T6 SAND CASTING (WAS 195)
52487	128	AL B195
52488	127	AL A218-F CASTINGS SAND
52489	36	AL 220-T4 CASTINGS SAND
52490	128	AL ALMAG-35-F CASTINGS SAND
52491	53	AL 357.0
52492	36	AL 218-F CASTINGS DIE
52493	53	AL 364-F CASTINGS DIE
52494	25	AL 2024-T3 SHEET 1 1/2% CLAD
52495	26	AL 2024-T351 PLATE 1 1/2% CLAD
52496	28	AL 2024-T361 PLATE 1 1/2% CLAD
52497	28	AL 2024-T361 SHEET 1 1/2% CLAD
52498	29	AL 2024-T42 PLATE BOTH SIDES 1 1/2% CLAD
52499	30	AL 2024-T42 SHEET BOTH SIDES 1 1/2% CLAD
52500	31	AL 2024-T62 PLATE 1 1/2% CLAD
52501	32	AL 2024-T62 SHEET 1 1/2% CLAD
52502	32	AL 2024-T72 SHEET 1 1/2% CLAD
52503	33	AL 2024-T81 SHEET 1 1/2% CLAD
52504	33	AL 2024-T851 PLATE 1 1/2% CLAD
52505	34	AL 2024-T861 PLATE 1 1/2% CLAD
52506	35	AL 2024-T861 SHEET 1 1/2% CLAD
52507	25	AL 2024-T3 SHEET ONE SIDE 1 1/2% CLAD
52508	26	AL 2024-T351 PLATE ONE SIDE 1 1/2% CLAD
52509	28	AL 2024-T361 PLATE ONE SIDE 1 1/2% CLAD
52510	28	AL 2024-T361 SHEET ONE SIDE 1 1/2% CLAD
52511	30	AL 2024-T42 PLATE ONE SIDE 1 1/2% CLAD
52512	30	AL 2024-T42 SHEET ONE SIDE 1 1/2% CLAD
52513	31	AL 2024-T62 PLATE ONE SIDE 1 1/2% CLAD
52514	32	AL 2024-T62 SHEET ONE SIDE 1 1/2% CLAD
52515	32	AL 2024-T72 SHEET ONE SIDE 1 1/2% CLAD
52516	33	AL 2024-T81 SHEET ONE SIDE 1 1/2% CLAD
52517	33	AL 2024-T851 PLATE ONE SIDE 1 1/2% ONE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005101 7

MATCD	PAGE	DESIGNATION
52518	35	AL 2024-T861 PLATE ONE SIDE 1 1/2% CLAD
52519	35	AL 2024-T861 SHEET ONE SIDE 1 1/2% CLAD
52520	111	AL 7075-T6 SHEET 2 1/2% CLAD
52521	112	AL 7075-T62 PLATE 2 1/2% CLAD
52522	113	AL 7075-T62 SHEET 2 1/2% CLAD
52523	114	AL 7075-T651 PLATE 2 1/2% CLAD
52524	117	AL 7075-T73 SHEET 2 1/2% CLAD
52525	118	AL 7075-T7351 PLATE 2 1/2% CLAD
52526	120	AL 7075-T76 SHEET 2 1/2% CLAD
52527	120	AL 7075-T7651 PLATE 2 1/2% CLAD
52528	111	AL 7075-T6 SHEET ONE SIDE 2 1/2% CLAD
52529	113	AL 7075-T62 PLATE ONE SIDE 2 1/2% CLAD
52530	113	AL 7075-T62 SHEET ONE SIDE 2 1/2% CLAD
52531	114	AL 7075-T651 PLATE ONE SIDE 2 1/2% CLAD
52532	111	AL 7075-T6 SHEET CLAD W/7008
52533	113	AL 7075-T62 PLATE W/7008 CLAD
52534	113	AL 7075-T62 SHEET CLAD W/7008
52535	114	AL 7075-T651 PLATE CLAD W/7008
52536	120	AL 7075-T76 SHEET CLAD W/7008
52537	120	AL 7075-T7651 PLATE CLAD W/7008
52540	9	AL 2011-T3 ROD COLD FINISHED
52541	10	AL 2011-T4 ROD COLD FINISHED
52542	10	AL 2011-T451 ROD COLD FINISHED
52543	11	AL 2011-T8 ROD COLD FINISHED
52544	9	AL 2011-T3 BAR COLD FINISHED
52545	10	AL 2011-T4 BAR COLD FINISHED
52546	10	AL 2011-T451 BAR COLD FINISHED
52547	11	AL 2011-T8 BAR COLD FINISHED
52548	10	AL 2011-T3 WIRE COLD FINISHED
52549	11	AL 2011-T8 WIRE COLD FINISHED
52550	10	AL 2011-T4 WIRE ROLLED
52551	10	AL 2011-T451 WIRE ROLLED
52552	10	AL 2011-T4 WIRE COLD FINISHED
52553	10	AL 2011-T451 WIRE COLD FINISHED
52554	3	AL 1060-O WIRE COLD FINISHED
52555	2	AL 1060-H14 WIRE COLD FINISHED
52556	2	AL 1060-H18 WIRE COLD FINISHED
52557	3	AL 1060-O ROD COLD FINISHED
52559	2	AL 1060-H18 ROD COLD FINISHED
52560	3	AL 1060-O BAR COLD FINISHED
52562	2	AL 1060-H18 BAR COLD FINISHED
52563	3	AL 1060-O TUBE EXTRUDED SEAMLESS
52564	3	AL 1060-O TUBE DRAWN SEAMLESS
52566	2	AL 1060-H14 TUBE DRAWN SEAMLESS
52567	2	AL 1060-H18 TUBE DRAWN SEAMLESS
52569	3	AL 1060-O PIPE
52570	1	AL 1060-H112 PIPE
52573	8	AL 1100-O WIRE COLD FINISHED
52574	7	AL 1100-O ROD COLD FINISHED
52575	7	AL 1100-O BAR COLD FINISHED
52576	6	AL 1100-H12 WIRE COLD FINISHED
52577	6	AL 1100-H14 WIRE COLD FINISHED
52578	7	AL 1100-H16 WIRE COLD FINISHED
52579	7	AL 1100-H18 WIRE COLD FINISHED
52580	5	AL 1100-H112 WIRE COLD FINISHED
52581	5	AL 1100-H112 ROD COLD FINISHED
52582	4	AL 1100-H112 BAR COLD FINISHED
52583	4	AL 1100-F WIRE COLD FINISHED
52584	4	AL 1100-F ROD COLD FINISHED
52585	4	AL 1100-F BAR COLD FINISHED
52586	8	AL 1100-O TUBE EXTRUDED SEAMLESS
52587	5	AL 1100-H112 TUBE EXTRUDED SEAMLESS
52588	5	AL 1100-H112 TUBE COILED EXTRUDED
52589	8	AL 1100-O TUBE DRAWN SEAMLESS
52590	5	AL 1100-H12 TUBE DRAWN SEAMLESS
52591	6	AL 1100-H16 TUBE DRAWN SEAMLESS
52592	7	AL 1100-H18 TUBE DRAWN SEAMLESS
52593	5	AL 1100-H113 TUBE DRAWN SEAMLESS
52594	57	AL 5050-O TUBE DRAWN SEAMLESS
52595	56	AL 5050-H32 TUBE DRAWN SEAMLESS
52596	56	AL 5050-H34 TUBE DRAWN SEAMLESS
52597	56	AL 5050-H36
52598	57	AL 5050-H38 TUBE DRAWN SEAMLESS
52599	56	AL 5005-O TUBE DRAWN SEAMLESS
52600	40	AL 2219-T851 BAR COLD FINISHED
52601	41	AL 2219-T851 ROD COLD FINISHED
52602	40	AL 2219-T62 WIRE EXTRUDED
52603	40	AL 2219-T62 ROD EXTRUDED
52604	40	AL 2219-T62 SHAPES EXTRUDED
52605	37	AL 2219-O TUBE EXTRUDED SEAMLESS
52606	38	AL 2219-T31 TUBE EXTRUDED SEAMLESS
52607	38	AL 2219-T3510 TUBE EXTRUDED SEAMLESS
52608	39	AL 2219-T3511 TUBE EXTRUDED SEAMLESS
52609	41	AL 2219-T8510 TUBE EXTRUDED SEAMLESS
52610	40	AL 2219-T62 TUBE EXTRUDED
52611	40	AL 2219-T81 TUBE EXTRUDED
52612	40	AL 2219-T62 TUBE EXTRUDED SEAMLESS
52613	40	AL 2219-T81 TUBE EXTRUDED SEAMLESS
52614	123	AL 7178-T6 SHEET CLAD W/7011
52615	124	AL 7178-T62 SHEET CLAD W/7011
52616	124	AL 7178-T651 PLATE CLAD W/7011
52617	125	AL 7178-T76 SHEET CLAD W/7011
52618	126	AL 7178-T7651 PLATE CLAD W/7011
52619	35	AL 2025-T6 FORGING
52620	190	STEEL 300M BAR 270-300 KSI UTS
52621	190	STEEL 300M FORGING 270-300 KSI UTS
52622	190	STEEL 300M TUBE 270-300 KSI UTS
52623	190	STEEL 300M CONSUMABLE VACUUM MELTED 270-300 KSI UTS
52624	190	STEEL 300M MACHINED FORGING 270-300 KSI UTS
52625	191	STEEL 300M WIRE 270-300 KSI UTS
52626	190	STEEL 300M BILLET 270-300 KSI UTS
52627		DELETED SEE 52620 - 52626
52628	198	STEEL 9NI 4CO (0.30C) SHEET QUENCHED AND TEMPERED
52629	198	STEEL 9NI 4CO (0.30C) STRIP QUENCHED AND TEMPERED
52630	198	STEEL 9NI 4CO (0.30C) PLATE QUENCHED AND TEMPERED
52631	198	STEEL 9NI 4CO (0.30C) PLATE 220-240 KSI UTS CVM
52632	198	STEEL 9NI 4CO (0.30C) PLATE 220-240 KSI UTS
52633	199	STEEL 9NI-4CO (.30C) ANNEALED
52634	198	STEEL 9NI 4CO (0.30C) SHEET 220-240 KSI UTS

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
52635	198	STEEL 9NI 4CO (0.30C) STRIP 220-240 KSI UTS
52636	198	STEEL 9NI 4CO (0.30C) TUBE 220-240 KSI UTS
52637	198	STEEL 9NI 4CO (0.30C) BAR 220-240 KSI UTS
52638	200	STEEL HY-TUF BAR QUENCHED AND TEMPERED > 200KSI
52639	200	STEEL HY-TUF FORGING QUENCHED AND TEMPERED > 200 KSI
52640	200	STEEL HY-TUF BAR COLD FINISHED
52641	200	STEEL HY-TUF FORGING COLD FINISHED
52642	200	STEEL HY-TUF QUENCHED AND TEMPERED 125-145KSI
52643	200	STEEL HY-TUF QUENCHED AND TEMPERED 150-170KSI
52644	201	STEEL HY-TUF QUENCHED AND TEMPERED 180-200KSI
52645	201	STEEL HY-TUF QUENCHED AND TEMPERED 200-220KSI
52646	201	STEEL HY-TUF QUENCHED AND TEMPERED 220-240KSI
52647	201	STEEL HY-TUF TUBE MECHANICAL
52648	199	STEEL 9NI 4CO (0.45C) FORGING LANDING GEAR 260-290 KSI UTS
52649	199	STEEL 9NI 4CO (0.45C) FORGING AUSTEMPERED
52650	198	STEEL 9NI 4CO (0.45C) ANNEALED
52651	199	STEEL 9NI 4CO (0.45C) FORGING 260-290 KSI UTS
52652	198	STEEL 9NI 4CO (0.45C) BAR 260-290 KSI UTS
52653	199	STEEL 9NI 4CO (0.45C) TUBE 260-290 KSI UTS
52654	199	STEEL 9NI 4CO (0.45C) FORGING QUENCHED/TEMPERED CVM
52655	199	STEEL 9NI 4CO (0.45C) FORGING 260-290 KSI UTS CVM
52656	199	STEEL 9NI 4CO (0.45C) FORGING AUSTEMPERED CVM
52657	199	STEEL 9NI 4CO (0.45C) PLATE AUSTEMPERED
52658	199	STEEL 9NI 4CO (0.45C) PLATE 260-290 KSI UTS
52659	199	STEEL 9NI 4CO (0.45C) PLATE AUSTEMPERED CVM
52660	199	STEEL 9NI 4CO (0.45C) PLATE QUENCHED/TEMPERED CVM
52661	199	STEEL 9NI 4CO (0.45C) PLATE 260-290 KSI UTS CVM
52662	199	STEEL 9NI 4CO (0.45C) BILLETS AUSTEMPERED FORGING
52663	199	STEEL 9NI 4CO (0.45C) FORGING DIE AUSTEMPERED
52664	198	STEEL 9NI 4CO (0.45C) BAR PREMIUM QUALITY CVM
52665	199	STEEL 9NI 4CO (0.45C) TUBE PREMIUM QUALITY CVM
52666	196	STEEL 9NI 4C0 (0.25C) SHEAR SPUN CASE 280-315 KSI TEMPERED
52667	196	STEEL 9NI 4C0 (0.25C) PLATE WELDED
52668	196	STEEL 9NI 4C0 (0.25C) PLATE 180-215 KSI UTS CVM
52669	196	STEEL 9NI 4C0 (0.25C) PLATE 180-215 KSI UTS
52670	196	STEEL 9NI 4C0 (0.25C) PLATE 235 KSI QUENCHED AND TEMPERED
52671	196	STEEL 9NI 4C0 (0.25C) PLATE WELDED/STRESS RELIEVED
52672	196	STEEL 9NI 4C0 (0.25C) ANNEALED
52673	197	STEEL 9NI 4C0 (0.25C) TUBE 180-215 KSI UTS
52674	196	STEEL 9NI 4C0 (0.25C) RINGS 180-215 KSI UTS
52675	197	STEEL 9NI 4C0 (0.25C) SHEET 180-215 KSI UTS
52676	197	STEEL 9NI 4C0 (0.25C) STRIP 180-215 KSI UTS
52677	196	STEEL 9NI 4C0 (0.25C) BAR 180-215 KSI UTS CVM
52678	196	STEEL 9NI 4C0 (0.25C) FORGING 180-215 KSI UTS CVM
52679	196	STEEL 9NI 4C0 (0.25C) FORGING 180-215 KSI UTS
52680	196	STEEL 9NI 4C0 (0.25C) BAR ANNEALED
52681	197	STEEL 9NI 4C0 (0.25C) TUBE PREMIUM QUALITY CVM
52682	196	STEEL 9NI 4C0 (0.25C) RINGS PREMIUM QUALITY CVM
52683	197	STEEL 9NI 4C0 (0.25C) SHEET PREMIUM QUALITY CVM
52684	196	STEEL 9NI 4C0 (0.20C) PLATE 180-215 KSI UTS CVM
52685	197	STEEL 9NI 4CO (0.20C) ANNEALED
52686	198	STEEL 9NI 4CO (0.20C) PLATE 180-215 KSI UTS
52687	197	STEEL 9NI 4CO (0.20C) BAR 180-215 KSI UTS
52688	197	STEEL 9NI 4CO (0.20C) FORGING 180-215 KSI UTS
52689	198	STEEL 9NI 4CO (0.20C) TUBE 180-215 KSI UTS
52690	197	STEEL 9NI 4CO (0.20C) 180-215 KSI UTS
52691	198	STEEL 9NI 4CO (0.20C) STRIP 180-215 KSI UTS
52692	197	STEEL 9NI 4CO (0.20C) BILLET 180-215 KSI UTS CVM
52693	198	STEEL 9NI 4CO (0.20C) PLATE WELDED
52694	198	STEEL 9NI 4CO (0.20C) ROD 180-215 KSI UTS CVM
52695	198	STEEL 9NI 4CO (0.20C) QUENCHED AND TEMPERED
52696	198	STEEL 9NI 4CO (0.25C) STRIP PREMIUM QUALITY CVM
52697	8	AL 1100-O TUBE DRAWN
52698	1	AL 1050-H112 TUBE EXTRUDED COILED
52699	189	STEEL 1025 SHEET COLD ROLLED
52700	189	STEEL 1025 STRIP COLD ROLLED
52701	189	STEEL 1025 TUBE COLD ROLLED
52702	189	STEEL 1025 BAR ALL
52703	202	STEEL T-1B PLATE
52704	170	CRES CK-20 CASTING ANNEALED
52705	170	CRES CK-20 CASTING ANNEALED HIGH TEMP SERVICE
52706	170	CRES CK-20 PIPE ANNEALED CENTRIFUGAL CAST
52708	172	CRES HK CASTING HIGH TEMP SERVICE
52709	172	CRES HK CAST TUBE CENTRIFUGAL
52710	172	CRES HK CASTING ANNEALED
52711	172	CRES HK AS CASTING
52712	161	CRES 317 ANNEALED
52717	161	CRES 321 FLAT EXTRUDED ANNEALED
52718	161	CRES 321 JOINTS BRAZED ANNEALED
52719	162	CRES 321 WIRE ANNEALED
52720	161	CRES 321 BAR COLD FINISHED
52721	159	CRES 314 WIRE ANNEALED
52722	160	CRES 314 WIRE COLD FINISHED
52723	159	CRES 314 BAR ANNEALED
52724	159	CRES 314 PLATE ANNEALED
52725	159	CRES 314 SHEET ANNEALED
52726	159	CRES 314 PLATE HOT ROLLED
52727	159	CRES 314 SHEET COLD ROLLED
52728	159	CRES 314 STRIP ANNEALED
52729	159	CRES 314 STRIP COLD ROLLED
52730	159	CRES 314 TUBE ANNEALED MECHANICAL
52731	159	CRES 314 TUBE COLD FINISHED MECHANICAL
52732	159	CRES 314 BAR COLD FINISHED
52733	159	CRES 314 BAR HOT FINISHED
52734	159	CRES 314 FORGING
52735	160	CRES 316 ANNEALED
52736	160	CRES 316 TUBE ANNEALED
52737	160	CRES 316 WIRE ANNEALED
52738	160	CRES 316 WIRE SOFT
52739	160	CRES 316 SPRING TEMPER
52740	160	CRES 316 FORGING ANNEALED
52741	160	CRES 316 CASTING
52742	160	CRES 316 MATERIAL BOLTING
52743	202	STEEL TOOL M50 BAR SPHEROIDIZE ANNEALED

MSFC-HDBK-527 REV F ■ 9999942 0005103 0 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
52744	202	STEEL TOOL M50 TUBE SPHEROIDIZE ANNEALED MECHANICAL
52745	202	STEEL TOOL M50 FORGING ANNEALED CVM
52746	202	STEEL TOOL M50 TUBE
52747	155	CRES 303SE BAR COLD FINISHED
52748	155	CRES 303SE BAR SOLUTION TREATED
52749	156	CRES 303SE WIRE SOLUTION TREATED
52750	155	CRES 303SE BOLTING MATERIAL SOLUTION TREATED
52751	156	CRES 303SE FORGING SOLUTION TREATED
52752	156	CRES 303SE CASTING SOLUTION TREATED
52753	155	CRES 303SE BAR HI-TENSION
52754	156	CRES 303SE WIRE SOFT
52755	156	CRES 303SE WIRE FULL HARD
52756	155	CRES 303SE BAR CAST
52757	183	MARAGING 18NI (200) SHEET STEEL AGED VAC REMELT
52758	182	MARAGING 18NI (200) PLATE STEEL AGED AIR MELT
52759	182	MARAGING 18NI (200) PLATE STEEL AGED VAC REMELT
52760	183	MARAGING 18NI (200) STEEL AGED AIR MELT HEAVY
52761	183	MARAGING 18NI (200) STEEL AGED VAC ARC REMELT
52762	183	MARAGING 18NI (200) STEEL ANNEALED
52763	183	MARAGING 18NI (200) ROUNDS STEEL AGED
52764	183	MARAGING 18NI (200) SHEET STEEL AGED
52765	183	MARAGING 18NI (200) STEEL AGED
52766	182	MARAGING 18NI (200) PLATE STEEL AGED
52767	183	MARAGING 18NI (200) STEEL PLATE WELDED AND AGED
52769	158	CRES 304L SHEET COLD ROLLED
52772		DELETED SEE 52773 - 52775,10157,10099,50810,50811
52773	162	CRES 347 BAR ANNEALED
52774	162	CRES 347 CASTING ANNEALED
52775	162	CRES 347 FORGING ANNEALED
52776	162	CRES 347 HOT EXTRUDED
52777		DELETED SEE 52778,52779
52778	152	CRES 201 SHEET ANNEALED
52779	152	CRES 201 STRIP ANNEALED
52780	152	CRES 201 SHEET 1/4 HARD
52781	152	CRES 201 STRIP 1/4 HARD
52782	152	CRES 201 SHEET 1/2 HARD
52783	152	CRES 201 STRIP 1/2 HARD
52784	152	CRES 201 SHEET 3/4 HARD
52785	62	AL 5052-O WIRE COLD FINISHED
52786	62	AL 5052-O ROD COLD FINISHED
52787	61	AL 5052-O BAR COLD FINISHED
52788	59	AL 5052-H32 WIRE COLD FINISHED
52789	60	AL 5052-H34 WIRE COLD FINISHED
52790	60	AL 5052-H36 WIRE COLD FINISHED
52791	61	AL 5052-H38 WIRE COLD FINISHED
52792	58	AL 5052-F ROD COLD FINISHED
52793	58	AL 5052-F BAR COLD FINISHED
52794	64	AL 5082-F WIRE COLD FINISHED
52795	62	AL 5052-O TUBE DRAWN SEAMLESS
52796	59	AL 5052-H32 TUBE DRAWN SEAMLESS
52797	60	AL 5052-H34 TUBE DRAWN SEAMLESS
52798	60	AL 5052-H36 TUBE DRAWN SEAMLESS
52799	61	AL 5052-H38 TUBE DRAWN SEAMLESS
52800	62	AL 5052-O TUBE DRAWN SEAMLESS SPECIAL TOLERANCE
52801	62	AL 5052-O TUBE DRAWN SEAMLESS HYDRAULIC
52802	62	AL 5052-O TUBE EXTRUDED SEAMLESS
52803	59	AL 5052-H32 TUBE WELDED
52804	60	AL 5052-H34 TUBE WELDED
52805	62	AL 5052-O TUBE ROUND
52806	59	AL 5052-H32 TUBE ROUND
52807	60	AL 5052-H34 TUBE ROUND
52808	60	AL 5052-H36 TUBE ROUND
52809	21	AL 2017-O BAR DRAWN
52810	21	AL 2017-T4 BAR DRAWN
52811	22	AL 2017-T42 BAR DRAWN
52812	22	AL 2017-T451 BAR DRAWN
52813	21	AL 2017-O BAR COLD FINISHED
52814	21	AL 2017-T4 BAR COLD FINISHED
52815	22	AL 2017-T42 BAR COLD FINISHED
52816	22	AL 2017-T451 BAR COLD FINISHED
52817	22	AL 2017-T42 ROD DRAWN
52818	23	AL 2017-T451 ROD DRAWN
52819	21	AL 2017-O ROD COLD FINISHED
52820	21	AL 2017-T4 ROD COLD FINISHED
52821	22	AL 2017-T42 ROD COLD FINISHED
52822	23	AL 2017-T451 ROD COLD FINISHED
52823	21	AL 2017-O WIRE DRAWN
52824	22	AL 2017-T4 WIRE DRAWN
52825	22	AL 2017-T42 WIRE DRAWN
52826	21	AL 2017-O WIRE COLD FINISHED
52827	22	AL 2017-T4 WIRE COLD FINISHED
52828	22	AL 2017-T42 WIRE COLD FINISHED
52829	21	AL 2017-O ROD DRAWN
52830	21	AL 2017-T4 ROD DRAWN
52831	23	AL 2017-T451 WIRE ROLLED
52833	68	AL 5086-O TUBE EXTRUDED SEAMLESS
52834	66	AL 5086-H111 TUBE EXTRUDED SEAMLESS
52835	67	AL 5086-H112 TUBE EXTRUDED SEAMLESS
52839	70	AL 5154-O ROD COLD FINISHED
52840	69	AL 5154-H112 ROD COLD FINISHED
52841	70	AL 5154-O BAR COLD FINISHED
52842	68	AL 5154-H112 BAR COLD FINISHED
52843	71	AL 5154-O WIRE COLD FINISHED
52844	69	AL 5154-H112 WIRE COLD FINISHED
52845	69	AL 5154-H32 WIRE COLD FINISHED
52846	70	AL 5154-H34 WIRE COLD FINISHED
52847	70	AL 5154-H36 WIRE COLD FINISHED
52848	70	AL 5154-H38 WIRE COLD FINISHED
52850	101	AL 6262-T6 WIRE COLD FINISHED
52851	100	AL 6262-T6 ROD COLD FINISHED
52852	100	AL 6262-T6 BAR COLD FINISHED
52853	101	AL 6262-T651 WIRE COLD FINISHED
52854	101	AL 6262-T651 ROD COLD FINISHED
52855	101	AL 6262-T651 BAR COLD FINISHED
52856	102	AL 6262-T9 WIRE COLD FINISHED
52857	102	AL 6262-T9 ROD COLD FINISHED
52858	89	AL 6062-T9 BAR COLD FINISHED
52859	101	AL 6262-T62 TUBE DRAWN SEAMLESS
52860	102	AL 6262-T9 TUBE DRAWN SEAMLESS

MSFC-HDBK-527 REV F 9999942 0005104 2

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
52861	100	AL 6262-T6 TUBE DRAWN SEAMLESS
52862	74	AL 5454-O TUBE EXTRUDED SEAMLESS
52863	73	AL 5454-H111 TUBE EXTRUDED SEAMLESS
52864	73	AL 5454-H112 TUBE EXTRUDED SEAMLESS
52865	73	AL 5454-H32 TUBE CONDENSER
52866	74	AL 5454-H34 TUBE CONDENSER
52871	129	AL C355.0-T61 CASTINGS PERMANENT MOLD
52872	48	AL 3003-O TUBE EXTRUDED SEAMLESS CLAD
52873	44	AL 3003-H112 TUBE EXTRUDED SEAMLESS CLAD
52874	50	AL 3004-O TUBE ROUND CLAD
52875	49	AL 3004-H32 TUBE ROUND CLAD
52876	49	AL 3004-H34 TUBE ROUND CLAD
52877	50	AL 3004-H36 TUBE ROUND CLAD
52878	63	AL 5056-H192 WIRE COLD FINISHED CLAD
52879	64	AL 5056-H392 WIRE COLD FINISHED CLAD
52880	64	AL 5056-H393 WIRE COLD FINISHED CLAD
52881	25	AL 2024-T3 SHEET ONE SIDE CLAD
52882	26	AL 2024-T351 PLATE ONE SIDE CLAD
52883	24	AL 2024-O SHEET ONE SIDE CLAD
52884	24	AL 2024-O PLATE ONE SIDE CLAD
52885	90	AL 6063-O TUBE EXTRUDED SEAMLESS
52886	90	AL 6063-T1 TUBE EXTRUDED SEAMLESS
52887	90	AL 6063-T1 TUBE ROUND EXTRUDED
52888	90	AL 6063-O TUBE DRAWN SEAMLESS
52889	91	AL 6063-T4 TUBE DRAWN SEAMLESS
52890	93	AL 6063-T6 TUBE STRUCTURAL EXTRUDED
52891	91	AL 6063-T42 TUBE DRAWN SEAMLESS
52892	93	AL 6063-T6 TUBE DRAWN SEAMLESS
52893	91	AL 6063-T4 TUBE EXTRUDED SEAMLESS
52894	91	AL 6063-T42 TUBE EXTRUDED SEAMLESS
52895	92	AL 6063-T5 TUBE EXTRUDED SEAMLESS
52896	93	AL 6063-T6 TUBE EXTRUDED SEAMLESS
52897	93	AL 6063-T62 TUBE DRAWN SEAMLESS
52898	94	AL 6063-T83 TUBE DRAWN SEAMLESS
52899	94	AL 6063-T831 TUBE DRAWN SEAMLESS
52900	94	AL 6063-T832 TUBE DRAWN SEAMLESS
52908	128	AL B218-F CASTINGS SAND
52909	109	AL 7075-O RIVET AND WIRE COLD HEADING
52910	109	AL 7075-O RIVET AND ROD COLD HEADING
52911	110	AL 7075-O WIRE COLD FINISHED
52912	109	AL 7075-O ROD ROLLED
52913	109	AL 7075-O ROD COLD FINISHED
52914	110	AL 7075-O WIRE DRAWN
52915	109	AL 7075-O ROD DRAWN
52916	118	AL 7075-T7351 BAR DRAWN
52917	119	AL 7075-T73511 TUBE EXTRUDED
52918	110	AL 7075-O WIRE EXTRUDED
52919	109	AL 7075-O ROD EXTRUDED
52920	110	AL 7075-O TUBE EXTRUDED SEAMLESS
52921	112	AL 7075-T6 TUBE EXTRUDED SEAMLESS
52922	114	AL 7075-T62 TUBE EXTRUDED SEAMLESS
52923	115	AL 7075-T6510 TUBE EXTRUDED SEAMLESS
52924	116	AL 7075-T6511 TUBE EXTRUDED SEAMLESS
52925	117	AL 7075-T73 TUBE EXTRUDED SEAMLESS
52926	118	AL 7075-T73510 TUBE EXTRUDED SEAMLESS
52927	119	AL 7075-T73511 TUBE EXTRUDED SEAMLESS
52928	110	AL 7075-T6 FORGING DIE
52929	119	AL 7075-T7352 FORGING DIE
52930	111	AL 7075-T6 FORGING HAND
52931	119	AL 7075-T7352 FORGING HAND
52932	109	AL 7075-O TUBE DRAWN SEAMLESS
52933	112	AL 7075-T6 TUBE DRAWN SEAMLESS
52934	113	AL 7075-T62 TUBE DRAWN SEAMLESS
52935	117	AL 7075-T73 TUBE DRAWN SEAMLESS
52937	127	AL A201.0-T7 CASTINGS SPECIAL MOLD
52938	127	AL A201.0-T4 CASTINGS PERMANENT MOLD
52939	127	AL A201.0-T4 CASTINGS SAND (WITH CHILLS)
52940	127	AL A201.0-T7 CASTINGS PERMANENT MOLD
52941	127	AL A201.0-T7 CASTINGS SAND
52942	51	AL 354.0-T4 CASTINGS SPECIAL MOLD
52943	51	AL 354.0-T4 CASTINGS SAND (WITH CHILLS)
52944	52	AL 354.0-T6 CASTINGS SPECIAL MOLD
52945	52	AL 354.0-T6 CASTINGS SAND (WITH CHILLS)
52946	52	AL 354.0-T61 CASTINGS SPECIAL MOLD
52947	52	AL 354.0-T61 CASTINGS SAND (WITH CHILLS)
52948	52	AL 354.0-T62 CASTINGS SPECIAL MOLD
52949	52	AL 354.0-T62 CASTINGS SAND (WITH CHILLS)
52950	128	AL A357.0-T6 CASTINGS INSULATED MOLD
52951	128	AL A357.0-T6 CASTINGS PERMANENT MOLD
52952	128	AL A357.0-T6 CASTINGS SPECIAL MOLD
52953	128	AL A357.0-T61 CASTINGS SAND
52954	128	AL A357.0-T61 CASTINGS PERMANENT MOLD
52955	128	AL A357.0-T61 CASTINGS SPECIAL MOLD
52956	123	AL 7178-O TUBE EXTRUDED SEAMLESS
52957	123	AL 7178-T6 TUBE EXTRUDED SEAMLESS
52958	125	AL 7178-T6510 TUBE EXTRUDED SEAMLESS
52959	125	AL 7178-T6511 TUBE EXTRUDED SEAMLESS
52960	124	AL 7178-T62 TUBE EXTRUDED SEAMLESS
52961	45	AL 3003-H12 SHEET
52962	45	AL 3003-H12 PLATE
52963	45	AL 3003-H14 SHEET
52964	45	AL 3003-H14 PLATE
52965	46	AL 3003-H16 SHEET
52966	46	AL 3003-H18 SHEET
52967	43	AL 3003-H112 PLATE
52968	48	AL 3003-O WIRE COLD FINISHED
52969	48	AL 3003-O ROD ROLLED
52970	48	AL 3003-O ROD COLD FINISHED
52971	47	AL 3003-O BAR ROLLED
52972	47	AL 3003-O BAR COLD FINISHED
52973	45	AL 3003-H12 WIRE ROLLED
52974	45	AL 3003-H12 WIRE COLD FINISHED
52975	46	AL 3003-H14 WIRE ROLLED
52976	46	AL 3003-H14 WIRE COLD FINISHED
52977	46	AL 3003-H16 WIRE ROLLED
52978	46	AL 3003-H16 WIRE COLD FINISHED
52979	47	AL 3003-H18 WIRE ROLLED
52980	47	AL 3003-H18 WIRE COLD FINISHED
52981	44	AL 3003-H112 WIRE ROLLED
52982	44	AL 3003-H112 WIRE COLD FINISHED

MSFC-HDBK-527 REV F ■ 9999942 0005105 4 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
52983	44	AL 3003-H112 ROD COLD FINISHED
52984	43	AL 3003-H112 BAR COLD FINISHED
52985	48	AL 3003-O SHAPES EXTRUDED
52986	44	AL 3003-H112 WIRE EXTRUDED
52987	44	AL 3003-H112 ROD EXTRUDED
52988	43	AL 3003-H112 BAR EXTRUDED
52989	44	AL 3003-H112 SHAPES EXTRUDED
52990	44	AL 3003-H112 TUBE EXTRUDED
52991	48	AL 3003-O TUBE EXTRUDED SEAMLESS
52992	44	AL 3003-H112 TUBE EXTRUDED SEAMLESS
52993	43	AL 3003-H112 PIPE
52994	46	AL 3003-H18 PIPE
52995	44	AL 3003-H112 TUBE ROUND EXTRUDED
52996	48	AL 3003-O TUBE DRAWN
52997	45	AL 3003-H12 TUBE DRAWN
52998	46	AL 3003-H14 TUBE DRAWN
52999	46	AL 3003-H16 TUBE DRAWN
53000	47	AL 3003-H18 TUBE DRAWN
53001	44	AL 3003-H113 TUBE DRAWN
53002	48	AL 3003-O TUBE DRAWN SEAMLESS
53003	45	AL 3003-H12 TUBE DRAWN SEAMLESS
53004	46	AL 3003-H14 TUBE DRAWN SEAMLESS
53005	46	AL 3003-H16 TUBE DRAWN SEAMLESS
53006	47	AL 3003-H18 TUBE DRAWN SEAMLESS
53007	44	AL 3003-H113 TUBE DRAWN SEAMLESS
53008	45	AL 3003-H14 TUBE CONDENSER
53009	47	AL 3003-H25 TUBE CONDENSER
53010	48	AL 3003-O TUBE WELDED
53011	45	AL 3003-H12 TUBE WELDED
53012	46	AL 3003-H16 TUBE WELDED
53013	47	AL 3003-H18 TUBE WELDED
53014	44	AL 3003-H112 TUBE WELDED
53017	47	AL 3003-O RIVET AND WIRE COLD HEADING
53018	47	AL 3003-O RIVET AND ROD COLD HEADING
53019	45	AL 3003-H14 RIVET AND WIRE COLD HEADING
53020	45	AL 3003-H14 RIVET AND ROD COLD HEADING
53021	43	AL 3003-H112 FORGING DIE
53022	47	AL 3003-H24 RIVET AND WIRE COLD HEADING
53023	47	AL 3003-H24 RIVET AND ROD COLD HEADING
53025	43	AL 2618-T61 ROLLED RINGS
53026	120	AL 7075-T76 SHEET
53027	14	AL 2014-T4 WIRE DRAWN
53028	17	AL 2014-T6 BAR ROLLED
53029	23	AL 2024-O BAR COLD FINISHED
53030	24	AL 2024-O TUBE DRAWN
53031	25	AL 2024-O TUBE EXTRUDED SEAMLESS
53032	24	AL 2024-O ROD COLD FINISHED
53033	25	AL 2024-O WIRE COLD FINISHED
53034	26	AL 2024-T3 TUBE EXTRUDED SEAMLESS
53035	25	AL 2024-T3 TUBE DRAWN
53036	26	AL 2024-T3 TUBE HYDRAULIC
53037	26	AL 2024-T351 BAR COLD FINISHED
53038	26	AL 2024-T351 ROD COLD FINISHED
53039	27	AL 2024-T3510 TUBE ROUND EXTRUDED
53040	27	AL 2024-T3510 TUBE EXTRUDED SEAMELSS
53041	27	AL 2024-T3510 WIRE EXTRUDED
53042	27	AL 2024-T3511 TUBE EXTRUDED SEAMLESS
53043	27	AL 2024-T3511 TUBE ROUND EXTRUDED
53044	27	AL 2024-T3511 WIRE EXTRUDED
53045	28	AL 2024-T36 WIRE COLD FINISHED
53046	28	AL 2024-T4 BAR COLD FINISHED
53047	28	AL 2024-T4 ROD COLD FINISHED
53048	29	AL 2024-T4 WIRE COLD FINISHED
53049	30	AL 2024-T42 TUBE EXTRUDED SEAMLESS
53050	29	AL 2024-T42 BAR COLD FINISHED
53051	30	AL 2024-T42 ROD COLD FINISHED
53052	30	AL 2024-T42 WIRE COLD FINISHED
53053	31	AL 2024-T6 ROD COLD FINISHED
53054	31	AL 2024-T6 WIRE ROLLED
53055	31	AL 2024-T62 BAR COLD FINISHED
53056	31	AL 2024-T62 ROD COLD FINISHED
53057	32	AL 2024-T62 WIRE COLD FINISHED
53058	32	AL 2024-T81 BAR EXTRUDED
53059	32	AL 2024-T81 ROD EXTRUDED
53060	33	AL 2024-T81 SHAPES EXTRUDED
53061	150	CRES 17PH-7MO RH950 200KSI MIN
53062	33	AL 2024-T81 TUBE EXTRUDED SEAMLESS
53063	33	AL 2024-T851 ROD COLD FINISHED
53064	33	AL 2024-T851 BAR COLD FINISHED
53065	34	AL 2024-T8510 SHAPES EXTRUDED
53066	34	AL 2024-T8511 WIRE EXTRUDED
53067	34	AL 2024-T8511 BAR EXTRUDED
53068	34	AL 2024-T8510 TUBE EXTRUDED SEAMLESS
53069	34	AL 2024-T8511 TUBE EXTRUDED SEAMLESS
53070	35	AL 2117-H13 RIVET AND ROD COLD HEADING
53071	36	AL 2117-T4 RIVET AND ROD COLD HEADING
53072	39	AL 2219-T6 FORGING
53073	43	AL 3003 TUBE WELDED CLAD
53075	68	AL 5145 ELECTRODES WELDING
53076	58	AL 5052-F WIRE COLD FINISHED
53077	71	AL 5183 ELECTRODES WELDING
53078	72	AL 5356 ELECTRODES WELDING
53083	37	AL 2219-O PLATE CLAD
53085	54	AL 4145 ELECTRODES WELDING
53086	152	CRES 201 STRIP 3/4 HARD
53087	152	CRES 201 SHEET FULL HARD
53088	152	CRES 201 STRIP FULL HARD
53089	152	CRES 201 COLD ROLLED
53090	176	INCOLOY 801 FORGING ANNEALED
53091	176	INCOLOY 801 FORGING AGED
53092	176	INCOLOY 801 PLATE ANNEALED
53093	176	INCOLOY 801 STRIP ANNEALED
53094	176	INCOLOY 801 TUBE WELDED AGED
53095	176	INCOLOY 801 TUBE AGED
53096	176	INCOLOY 801 BAR AGED
53097	176	INCOLOY 801 JOINT WELDED
53098	176	INCOLOY 801 RINGS FLASH WELDED
53099	176	INCOLOY 801 STOCK
53100	187	RA-330HC ALLOY PLATE ANNEALED
53101	187	RA-330HC ALLOY BAR ANNEALED

MSFC-HDBK-527 REV F ■ 9999942 0005106 6 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
53102	187	RA-330HC ALLOY STOCK ANNEALED
53103	201	STEEL RA-330HC ALLOY STOCK QUENCHED AND TEMPERED
53104	147	CRES 16-15-6
53105	169	CRES AFC-77 BAR QUENCHED AND TEMPERED
53106	169	CRES AFC-77 SHEET
53107	169	CRES AFC-77 ANNEALED
53108	200	STEEL HNM BAR ANNEALED
53109	200	STEEL HNM BAR ANNEALED AND AGED
53110	167	CRES 440F WIRE COLD FINISHED
53111	167	CRES 440F BAR ANNEALED
53112	167	CRES 440F CASTINGS INVESTMENT ANNEALED
53113	167	CRES 440F CASTINGS INVESTMENT QUENCHED AND TEMPERED
53114	170	CRES AM-363 SHEET ANNEALED
53115	170	CRES AM-363 SHEET HOT ROLLED
53116	173	CRES V-57 BAR SOLUTION TREATED 172 KSI
53117	173	CRES V-57 BAR AGED 93 KSI
53118	140	CRES 12CR-0.5MO BAR TEMPERED
53119	140	CRES 12CR-0.5MO FORGING TEMPERED
53120	140	CRES 12CR-0.5MO STOCK FORGING TEMPERED
53121	196	STEEL 98BV40 BAR >200KSI UTS
53122	196	STEEL 98BV40 FORGING >200KSI UTS
53123	196	STEEL 98BV40 TUBE >200KSI UTS
53124	196	STEEL 98BV40 ALL 280KSI UTS
53125	152	CRES 203EZ WIRE ANNEALED
53126	152	CRES 203EZ WIRE COLD FINISHED
53127	152	CRES 203EZ BAR COLD FINISHED
53128	152	CRES 203EZ BAR FULL HARD
53129	167	CRES 440C WIRE ANNEALED
53130	167	CRES 440C WIRE SOFT
53131	167	CRES 440C CASTINGS INVESTMENT ANNEALED
53132	166	CRES 440B BAR COLD FINISHED
53133	166	CRES 440B WIRE ANNEALED
53134	166	CRES 440B WIRE SOFT
53135	166	CRES 440B CASTINGS INVESTMENT ANNEALED
53136	166	CRES 440B CASTINGS INVESTMENT QUENCHED & TEMPERED
53137	166	CRES 440A BAR COLD FINISHED
53138	166	CRES 440A WIRE ANNEALED
53139	166	CRES 440A WIRE SOFT
53140	166	CRES 440A FORGING ANNEALED
53141	166	CRES 440A CASTINGS INVESTMENT ANNEALED
53142	166	CRES 440A CASTINGS INVESTMENT QUENCHED & TEMPERED
53143	140	CRES 12.5CR-1W BAR ANNEALED & TEMPERED
53144	140	CRES 12.5CR-1W FORGING ANNEALED & TEMPERED
53145	140	CRES 12.5CR-1W FORGING STOCK ANNEALED & TEMPERED
53146	173	CRES N-155 SHEET ANNEALED
53147	173	CRES N-155 TUBE WELDED ANNEALED
53148	172	CRES N-155 CASTINGS PRECISION INVESTMENT AS CAST
53149	172	CRES N-155 BAR AGED
53150	172	CRES N-155 BAR ANNEALED
53151	172	CRES N-155 FORGING ANNEALED
53152	172	CRES N-155 FORGING AGED
53153	173	CRES N-155 STRIP ANNEALED
53154	172	CRES N-155 PLATE ANNEALED
53155	173	CRES N-155 TUBE ANNEALED
53156	191	STEEL 4135 SHEET NORMALIZED
53157	191	STEEL 4135 STRIP NORMALIZED
53158	191	STEEL 4135 PLATE NORMALIZED
53159	191	STEEL 4135 TUBE NORMALIZED
53160	191	STEEL 4135 ROUND QUENCHED & TEMPERED
53161	191	STEEL 4135 SHEET QUENCHED & TEMPERED
53162	191	STEEL 4135 TUBE QUENCHED & TEMPERED
53163	191	STEEL 4135 ALL 125 KSI UTS
53164	191	STEEL 4135 ALL 150 KSI UTS
53165	191	STEEL 4135 ALL 180 KSI UTS
53166	195	STEEL 8740 SHEET <200 KSI UTS
53167	195	STEEL 8740 STRIP <200 KSI UTS
53168	195	STEEL 8740 PLATE <200 KSI UTS
53169	195	STEEL 8740 BAR <200 KSI UTS
53170	195	STEEL 8740 FORGING <200 KSI UTS
53171	195	STEEL 8740 RINGS <200KSI
53172	195	STEEL 8740 TUBE <200 KSI UTS
53173	173	DELETED SEE 52170
53174	173	DELETED SEE 53170
53175	195	STEEL 8740 ALL 180 KSI UTS
53176	195	STEEL 8740 ALL 200 KSI UTS
53177	192	STEEL 4330SI WROUGHT QUENCHED & TEMPERED
53178	192	STEEL 4330SI SHEET QUENCHED & TEMPERED
53179	192	STEEL 4330SI ALL 125 KSI UTS
53180	192	STEEL 4330SI ALL 150 KSI UTS
53181	192	STEEL 4330SI ALL 180 KSI UTS
53182	192	STEEL 4330SI ALL 200 KSI UTS
53183	192	STEEL 4330SI ALL 220 KSI UTS
53184	176	INCOLOY 802 ROUNDS ANNEALED
53185	176	INCOLOY 802 PLATE ANNEALED
53186	176	INCOLOY 802 TUBE EXTRUDED ANNEALED
53187	176	INCOLOY 802 ANNEALED
53188	176	INCOLOY 802 SHAPES ANNEALED & AGED
53189	176	INCOLOY 802 PLATE ANNEALED & AGED
53190	194	STEEL 8735 SHEET NORMALIZED
53191	194	STEEL 8735 STRIP NORMALIZED
53192	194	STEEL 8735 PLATE NORMALIZED
53193	194	STEEL 8735 BARS
53194	194	STEEL 8735 FORGING
53195	195	STEEL 8735 TUBE NORMALIZED
53196	194	STEEL 8735 SHEET <180 KSI UTS
53197	194	STEEL 8735 ROUNDS <180 KSI UTS
53198	195	STEEL 8735 TUBE <180 KSI UTS
53202	170	CRES CUSTOM 450 BAR ANNEALED
53203	171	CRES CUSTOM 450 H900 BAR
53204	170	CRES CUSTOM 450 H1050 BAR
53205	171	CRES CUSTOM 450 H950 BAR
53206	170	CRES CUSTOM 450 H1000 BAR
53207	170	CRES CUSTOM 450 H1100 BAR
53208	171	CRES CUSTOM 450 H1150 BAR
53209	177	INCOLOY SHEET DEEP DRAWN
53210	177	INCOLOY STRIP DEEP DRAWN
53211	177	INCOLOY SHEET ANNEALED
53212	177	INCOLOY TUBE ANNEALED
53213	177	INCOLOY STRIP ANNEALED

MSFC-HDBK-527 REV F 9999942 0005107 8

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
53214	177	INCOLOY PLATE ANNEALED
53215	176	INCOLOY BAR ANNEALED
53216	177	INCOLOY WIRE ANNEALED
53217	177	INCOLOY PLATE HOT ROLLED
53218	177	INCOLOY BAR HOT ROLLED
53219	177	INCOLOY BAR HOT WORKED
53220	177	INCOLOY BAR COLD DRAWN
53221	202	STEEL T-1A PLATE WELDED
53222	202	STEEL T-1A PLATE WELDED & TEMPERED
53223	202	STEEL T-1A SHEET
53224	202	STEEL T-1A STRIP
53225	202	STEEL T-1A PLATE <180 KSI UTS
53226	164	CRES 416 CASTINGS PRECISION INVESTMENT QUENCHED & TEMPERED
53227	164	CRES 416 WIRE ANNEALED
53228	164	CRES 416 WIRE COLD FINISHED
53229	164	CRES 416 WIRE QUENCHED & TEMPERED
53230	164	CRES 416 FORGING ANNEALED
53231	163	CRES 403 SHEET ANNEALED
53232	163	CRES 403 STRIP
53233	163	CRES 403 PLATE ANNEALED
53234	163	CRES 403 BAR ANNEALED
53235	163	CRES 403 BAR TEMPERED
53236	163	CRES 403 BAR COLD DRAWN
53237	163	CRES 403 WIRE ANNEALED
53238	163	CRES 403 WIRE COLD DRAWN
53239	163	CRES 403 WIRE TEMPERED
53240	163	CRES 403 BILLET
53241	185	NITRALLOY 135MOD BAR HOT ROLLED
53242	185	NITRALLOY 135MOD BAR COLD ROLLED
53243	185	NITRALLOY 135MOD FORGING
53244	185	NITRALLOY 135MOD FORGING STOCK
53245	185	NITRALLOY 135MOD BAR QUENCHED & NITRIDED
53246	195	STEEL 9310 BAR ANNEALED
53247	195	STEEL 9310 BAR NORMALIZED
53248	201	STEEL T-1 PLATE <180 KSI UTS
53249	201	STEEL T-1 PLATE WELDED
53250	201	STEEL T-1 PLATE UNWELDED
53251	201	STEEL T-1 PLATE WELDED & TEMPERED
53252	201	STEEL T-1 BAR <180 KSI UTS
53253	201	STEEL T-1 FLATS <180 KSI UTS
53254	201	STEEL T-1 TUBE SEAMLESS <180 KSI UTS
53255	202	STEEL T-1 WROUGHT <180 KSI UTS
53256	201	STEEL T-1 STRIP
53257	140	CRES 12CR FERRITE CONTROLLED SHEET ANNEALED
53258	140	CRES 12CR FERRITE CONTROLLED STRIP ANNEALED
53259	140	CRES 12CR FERRITE CONTROLLED PLATE ANNEALED
53260	140	CRES 12CR FERRITE CONTROLLED BAR QUENCHED & TEMPERED
53261	140	CRES 12CR FERRITE CONTROLLED FORGING QUENCHED & TEMPERED
53262	140	CRES 12CR FERRITE CONTROLLED TUBE QUENCHED & TEMPERED
53263	140	CRES 12CR FERRITE CONTROLLED FORGING STOCK QUENCHED & TEMPERED
53264	165	CRES 431 CASTING ANNEALED
53265	165	CRES 431 CASTING QUENCHED & TEMPERED
53266	165	CRES 431 CASTING PRECISION QUENCHED & TEMPERED
53267	165	CRES 431 WIRE COLD FINISHED
53268	165	CRES 431 BAR COLD FINISHED
53269	165	CRES 431 TUBING MECHANICAL COLD FINISHED
53270	165	CRES 431 BILLET QUENCHED & TEMPERED
53271	165	CRES 431 BAR HOT FINISHED
53272	165	CRES 431 CASTING INVESTMENT HOT FINISHED
53273	165	CRES 431 CASTING NORMALIZED & TEMPERED
53274	165	CRES 431 CASTING INVESTMENT NORMALIZED & TEMPERED
53275	165	CRES 431 WIRE SOFT
53276	165	CRES 431 CASTING AS CAST
53277	176	INCOLOY 800H BAR ANNEALED
53278	176	INCOLOY 800H BAR COLD WORKED
53279	176	INCOLOY 800H BAR AGED
53280	176	INCOLOY 800H BAR COLD WORKED AND AGED
53281	169	CRES AM-350 CONDITION H
53282	169	CRES AM-350 SCT ALL
53283	169	CRES AM-350 SCT850 SHEET
53284	169	CRES AM-350 SCT850 STRIP
53285	170	CRES AM-350 SHEET COLD ROLLED & TEMPERED
53286	170	CRES AM-350 SHEET CONDITION H
53287	170	CRES AM-350 STRIP COLD ROLLED & TEMPERED
53288	170	CRES AM-350 STRIP CONDITION H
53289	170	CRES AM-350 TUBE DA
53290	169	CRES AM-350 SCT1000 BAR
53291	169	CRES AM-350 SCT1000 FORGING
53292	169	CRES AM-350 SCT850 BAR
53293	169	CRES AM-350 BAR DA
53294	170	CRES AM-350 SHEET CONDITION L
53295	170	CRES AM-350 SHEET DA
53296	169	CRES AM-350 SHEET AS WELDED
53297	170	CRES AM-350 SHEET WELD AND HEAT TREATED
53298	170	CRES AM-350 SHEET BRAZED AND HEAT TREATED
53299	169	CRES AM-350 ELECTRODES WELDING
53300	170	CRES AM-350 WIRE WELDING
53301	163	CRES 410CB BAR QUENCHED & TEMPERED
53302	163	CRES 410CB BAR ANNEALED
53303	163	CRES 410CB FORGING QUENCHED & TEMPERED
53304	164	CRES 410CB TUBING MECHANICAL QUENCHED & TEMPERED
53305	163	CRES 410CB FORGING STOCK QUENCHED & TEMPERED
53306	172	CRES GREEK ASCOLOY SHEET ANNEALED
53307	172	CRES GREEK ASCOLOY STRIP ANNEALED
53308	171	CRES GREEK ASCOLOY PLATE ANNEALED
53309	172	CRES GREEK ASCOLOY WIRE COLD FINISHED
53310	171	CRES GREEK ASCOLOY CASTINGS INVESTMENT QUENCHED & TEMPERED
53311	171	CRES GREEK ASCOLOY BAR ANNEALED
53312	171	CRES GREEK ASCOLOY BILLET ANNEALED
53313	171	CRES GREEK ASCOLOY FLAT EXTRUDED ANNEALED
53314	171	CRES GREEK ASCOLOY FLAT EXTRUDED QUENCHED & TEMPERED
53315	172	CRES GREEK ASCOLOY RINGS WELDED ANNEALED
53316	172	CRES GREEK ASCOLOY TUBE COLD FINISHED

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005108 T ■

MATCD	PAGE	DESIGNATION
53317	172	CRES GREEK ASCOLOY SHEET QUENCHED & TEMPERED
53318	172	CRES GREEK ASCOLOY STRIP QUENCHED & TEMPERED
53319	171	CRES GREEK ASCOLOY PLATE QUENCHED & TEMPERED
53320	172	CRES GREEK ASCOLOY WELD METAL QUENCHED & TEMPERED
53322	172	CRES GREEK ASCOLOY QUENCHED & TEMPERED
53323	151	CRES 17PH-7MO TH1050 SHEET
53324	151	CRES 17PH-7MO TH1050 STRIP
53325	150	CRES 17PH-4MO PLATE TH1050
53327		DELETED SEE 10409
53328		DELETED SEE 50750
53329	151	CRES 17PH-7MO TUBE WELDED CONDITION A
53330	151	CRES 17PH-7MO TH1050 TUBE WELDED
53331	150	CRES 17PH-7MO RH950 SHEET
53332	151	CRES 17PH-7MO RH950 STRIP
53333	150	CRES 17PH-7MO RH950 PLATE
53334	150	CRES 17PH-7MO PLATE CONDITION C
53335	150	CRES 17PH-7MO CH900 PLATE
53336	150	CRES 17PH-7MO CONDITION T
53337	151	CRES 17PH-7MO TH1050
53338	150	CRES 17PH-7MO A1750
53339	150	CRES 17PH-7MO R100
53340	150	CRES 17PH-7MO BAR CONDITION A
53341	150	CRES 17PH-7MO FORGING CONDITION A
53342	175	INCOLOY 800 FORGING
53343	175	INCOLOY 800 PIPE ANNEALED
53344	175	INCOLOY 800 PIPE COLD DRAWN & ANNEALED
53345	175	INCOLOY 800 PIPE 1/2 HARD
53346	175	INCOLOY 800 PIPE FULL HARD
53347	175	INCOLOY 800 TUBE SEAMLESS ANNEALED
53348	175	INCOLOY 800 TUBE SEAMLESS COLD DRAWN & ANNEALED
53349	175	INCOLOY 800 TUBE SEAMLESS 1/2 HARD
53350	176	INCOLOY 800 TUBE SEAMLESS FULL HARD
53351	175	INCOLOY 800 ROD HOT FINISHED
53352	175	INCOLOY 800 ROD COLD DRAWN & ANNEALED
53353	175	INCOLOY 800 BAR HOT FINISHED
53354	175	INCOLOY 800 BAR COLD DRAWN & ANNEALED
53355	175	INCOLOY 800 PLATE ANNEALED
53356	175	INCOLOY 800 PLATE AS ROLLED
53357	175	INCOLOY 800 PLATE ANNEALED
53358	175	INCOLOY 800 SHEET AS ROLLED
53359	175	INCOLOY 800 SHEET COLD DRAWN & ANNEALED
53360	175	INCOLOY 800 STRIP COLD DRAWN & ANNEALED
53361	145	CRES 14PH-8MO SRH950 SHEET
53362	145	CRES 14PH-8MO SRH950 STRIP
53363	145	CRES 14PH-8MO SRH1050 SHEET
53364	145	CRES 14PH-8MO SRH1050 STRIP
53365	145	CRES 14PH-8MO SRH950 SHEET AIR MELT
53366	145	CRES 14PH-8MO SRH1050 SHEET AIR MELT
53367	145	CRES 14PH-8MO SHEET AIR MELT AGED
53368	144	CRES 14PH-8MO BCHT1050 SHEET AIR MELT
53369	144	CRES 14PH-8MO CH900 SHEET AIR MELT
53370	144	CRES 14PH-8MO CH1050 SHEET AIR MELT
53371	145	CRES 14PH-8MO SHEET CONDITION A
53372	145	CRES 14PH-8MO STRIP CONDITION A
53373	145	CRES 14PH-8MO SHEET CONDITION C
53374	145	CRES 14PH-8MO STRIP CONDITION C
53375	144	CRES 14PH-8MO CH900 SHEET
53376	144	CRES 14PH-8MO CH900 STRIP
53377	144	CRES 14PH-8MO CH900 STRIP
53378	144	CRES 14PH-8MO CH950 STRIP
53379	144	CRES 14PH-8MO CH950 SHEET AIR MELT
53380	145	CRES 14PH-8MO SRH950 SHEET CVM
53381	145	CRES 14PH-8MO SRH1050 SHEET CVM
53382	144	CRES 14PH-8MO BCHT950 SHEET CVM
53383	145	CRES 14PH-8MO SHEET CVM ELECTRON BEAM WELDED
53384	144	CRES 14PH-8MO BCHT1050 SHEET CVM
53385	151	CRES 18-8 SHEET AIR MELT BRAZING-CYCLE HEAT TREATED
53386	145	CRES 14PH-8MO SHEET CVM BRAZING-CYCLE HEAT TREATED
53387	147	CRES 15PH-5MO H900 FORGING
53388	147	CRES 15PH-5MO H925 BAR
53389	147	CRES 15PH-5MO H925 FORGING
53390	146	CRES 15PH-5MO H1100 BAR
53391	146	CRES 15PH-5MO H1100 FORGING
53392	146	CRES 15PH-5MO H900 AIR MELTED
53393	147	CRES 15PH-5MO H925 AIR MELTED
53394	145	CRES 15PH-5MO H1025 AIR MELTED
53395	145	CRES 15PH-5MO H1015 AIR MELTED
53396	146	CRES 15PH-5MO H1100 AIR MELTED
53397	146	CRES 15PH-5MO H1150 AIR MELTED
53398	146	CRES 15PH-5MO H1150M AIR MELTED
53399	147	CRES 15PH-5MO H900 RINGS FLASH WELDED
53400	147	CRES 15PH-5MO H900 FORGING STOCK
53401	147	CRES 15PH-5MO SHAPES CONDITION A
53402	147	CRES 15PH-5MO H900 ROUNDS
53403	147	CRES 15PH-5MO H900 BAR CVM
53404	145	CRES 15PH-5MO H1025 BAR CVM
53405	146	CRES 15PH-5MO H1150 BAR CVM
53406	146	CRES 15PH-5MO H900 BAR AIR MELT
53407	145	CRES 15PH-5MO H1025 BAR AIR MELT
53408	146	CRES 15PH-5MO H1150 BAR AIR MELT
53409	145	CRES 15PH-5MO FLATS CONDITION A
53410	147	CRES 15PH-5MO H900 ELECTRODE CONSUMABLE BAR
53411	147	CRES 15PH-5MO H925 ELECTRODE CONSUMABLE BAR
53412	145	CRES 15PH-5MO H1025 ELECTRODE CONSUMABLE BAR
53413	146	CRES 15PH-5MO H1075 ELECTRODE CONSUMABLE BAR
53414	146	CRES 15PH-5MO H1100 ELECTRODE CONSUMABLE BAR
53415	146	CRES 15PH-5MO H1150 ELECTRODE CONSUMABLE BAR
53416	146	CRES 15PH-5MO H1150M ELECTRODE CONSUMABLE BAR
53417	147	CRES 15PH-5MO H900 WIRE
53418	168	CRES A286 SHEET ANNEALED
53419	169	CRES A286 STRIP ANNEALED
53420	168	CRES A286 PLATE ANNEALED
53421	169	CRES A286 STRIP 140KSI UTS
53422	169	CRES A286 TUBE 130-140KSI UTS
53423	167	CRES A286 AGED
53424	168	CRES A286 COLD REDUCED
53425	168	CRES A286 BAR ANNEALED
53426	168	CRES A286 BAR QUENCHED
53427	168	CRES A286 BAR >140KSI UTS

MSFC-HDBK-527 REV F 9999942 0005109 1

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
53428	169	CRES A286 STOCK >140KSI, UTS
53429	168	CRES A286 SHEET >140KSI, UTS
53430	168	CRES A286 RINGS 130-140KSI, UTS
53431	141	CRES 13PH-8MO CONDITION A
53432	144	CRES 13PH-8MO H950 WIRE
53433	144	CRES 13PH-8MO RH950 BAR
53434	143	CRES 13PH-8MO H1150 BAR
53435	143	CRES 13PH-8MO H1150M BAR
53436	141	CRES 13PH-8MO A950
53437	140	CRES 13PH-8MO A1000
53438	140	CRES 13PH-8MO A1050
53439	140	CRES 13PH-8MO A1100
53440	144	CRES 13PH-8MO ORH950
53441	141	CRES 13PH-8MO H1000 SHEET
53442	141	CRES 13PH-8MO BCHT950 FORGING
53443	144	CRES 13PH-8MO H950 PLATE
53444	144	CRES 13PH-8MO PLATE WELDED & HEAT TREATED
53445	141	CRES 13PH-8MO H1000 PLATE
53446	143	CRES 13PH-8MO H950 BAR ROUND
53447	143	CRES 13PH-8MO H950 BAR HEX
53448	143	CRES 13PH-8MO H950 BAR SQUARE
53449	143	CRES 13PH-8MO H950 BAR FLAT
53450	141	CRES 13PH-8MO H1000 BAR ROUND
53451	141	CRES 13PH-8MO H1000 BAR HEX
53452	141	CRES 13PH-8MO H1000 BAR SQUARE
53453	141	CRES 13PH-8MO H1000 BAR FLAT
53454	141	CRES 13PH-8MO H1025 BAR ROUND
53455	141	CRES 13PH-8MO H1025 BAR HEX
53456	141	CRES 13PH-8MO H1025 BAR SQUARE
53457	141	CRES 13PH-8MO H1025 BAR FLAT
53458	142	CRES 13PH-8MO H1050 BAR ROUND
53459	142	CRES 13PH-8MO H1050 BAR HEX
53460	142	CRES 13PH-8MO H1050 BAR SQUARE
53461	142	CRES 13PH-8MO H1050 BAR FLAT
53462	142	CRES 13PH-8MO H1100 BAR ROUND
53463	142	CRES 13PH-8MO H1100 BAR HEX
53464	142	CRES 13PH-8MO H1100 BAR SQUARE
53465	142	CRES 13PH-8MO H1100 BAR FLAT
53466	143	CRES 13PH-8MO H1150 BAR ROUND
53467	143	CRES 13PH-8MO H1150 BAR HEX
53468	143	CRES 13PH-8MO H1150 BAR SQUARE
53469	143	CRES 13PH-8MO H1150 BAR FLAT
53470	144	CRES 13PH-8MO H950 RINGS FLASH WELDED
53471	143	CRES 13PH-8MO H950 EXTRUSIONS
53472	141	CRES 13PH-8MO H1000 RINGS FLASH WELDED
53473	141	CRES 13PH-8MO H1000 EXTRUSIONS
53474	142	CRES 13PH-8MO H1025 RINGS FLASH WELDED
53475	142	CRES 13PH-8MO H1025 EXTRUSIONS
53476	142	CRES 13PH-8MO H1050 RINGS FLASH WELDED
53477	142	CRES 13PH-8MO H1050 EXTRUSIONS
53478	143	CRES 13PH-8MO H1100 FORGING
53479	143	CRES 13PH-8MO H1100 RINGS FLASH WELDED
53480	143	CRES 13PH-8MO H1100 EXTRUSIONS
53481	143	CRES 13PH-8MO H1150 FORGING
53482	144	CRES 13PH-8MO RINGS FLASH WELDED
53483	143	CRES 13PH-8MO H1150 EXTRUSIONS
53484	144	CRES 13PH-8MO H950 STRIP
53485	141	CRES 13PH-8MO H1000 STRIP
53486	142	CRES 13PH-8MO H1050 STRIP
53487	144	CRES 13PH-8MO STRIP WELDED AND HEAT TREATED

MSFC-HDBK-527 REV F ■ 9999942 0005110 8 ■

Information Handling Services, 2000

TABLE 2

NONMETALS

Information Handling Services, 2000

TABLE 2A

NONMETALS BY DESIGNATION

Information Handling Services, 2000

60103 ABLATIVE C/FIB FIBERITE MXC313 SPEC: STW5-2687
MANF:
....NO TEST DATA AVAILABLE....

62317 ABLATIVE COMPOUND EPOXY PD451A GID: AWBGXX
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.1E-6	1.43	.00	.63	72H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60105 ABLATIVE COMPOUND PHENOLIC/SILICONE SPEC: STW5-2667
MANF: AQM
....NO TEST DATA AVAILABLE....

60279 ABLATIVE MA255 T1
MANF: AQM
....NO TEST DATA AVAILABLE....

06347 ABLATOR 5026-39H/C-G
....NO TEST DATA AVAILABLE....

06346 ABLATOR 5026-39M

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.29	.49	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

85467 ABLATOR BTA BOOSTER TROWELLABLE/EC2216/GLASS SPHERE/CORK SPEC: USBI10753-0032
MANF: USBI
....NO TEST DATA AVAILABLE....

65299 ABLATOR MA-25/FRL-IV GID: CAXXXX
MANF: FABRIC RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	015.0				15.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62714 ABLATOR MSA-2 SPRAYABLE GID: PTXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.500	0.125		05.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62713 ABLATOR MTA-3 TROWELLABLE GID: EWXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.343			00.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06035 ABLATOR SLA 561 GID: DTFRXX
MANF: MARTIN MARIETTA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.100		00.00	00.00	NONE
I	1	025.0	014.7	0.100		00.17	12.00 T	NONE
I	1	025.0	014.7	0.500		00.05	12.00 T	NONE
I	1	025.9	014.3	0.186		00.30	06.00 T	NONE
I	1	030.0	009.0	0.100		00.17	12.00 T	NONE
I	1	030.0	014.7	0.500		00.22	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR

RT	RT WEIGHT	CURE
X	00022.60	

TOXICITY

Information Handling Services, 2000

69911 ABLEFILM 561 EPOXY ON GLASS 8/VERSAMID 115

MANF: SHELL CHEMICAL/COAST PRO SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.002	0.008		05.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.63	.02	.00	4.5H-70F- 4H-149F-

ODOR

RT	RT	WEIGHT	CURE
	B	27.04	4H-150F-

TOXICITY

62355 ABSORBER AFONIC VIBRASORB GID: AAXXXX

MANF: E N MURRAY COMPANY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	V	00041.43	

TOXICITY

01897 ABSORBER CO2 LITHIUM HYDROXIDE

MANF: FOOTE MINERAL CO

....NO TEST DATA AVAILABLE....

62296 ABSORBER ENERGY EAR 1002 GID: AAXXXX

MANF: EAR CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.132	0.010		01.30	NONE
A	1	030.0	009.0	0.132	0.010		01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	B	00021.34	24H-70F- 24H-150F-

TOXICITY

62297 ABSORBER ENERGY EAR C2003/ADH GID: AAXXXX

MANF: EAR CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.057	0.010		02.60	NONE
A	1	030.0	009.0	0.057	0.010		02.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00020.76	

TOXICITY

06224 ABSORBER RF IRON/EPOXY GID: AABGMI

....NO TEST DATA AVAILABLE....

06134 ABSORBER RF IRON/EPOXY EMA 719 GID: AABGMI

MANF: SIB DIELECTRIC COMM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.261		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-7	.08	.01		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

03467 ABSORBER SILICA GEL

....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005114 5

Information Handling Services, 2000

60919 ABSORBER SOUND GP-2 DAMPING GID: AAXXXX
MANF: SOUNDCOAT

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.062	0.010		01.50	SMALL	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							X	20.86	

20026 ACID LAURIC GID: AIXXXX
MANF: AQM
....NO TEST DATA AVAILABLE....

60745 ACOUSTA STYLE 200 GID: DVXXXX
MANF: GOODYEAR

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.108			02.90	SMALL	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	2.0E-6	7.05	2.82	.05		A	A	00020.73	

62266 ACRYLIC CUVETTE 749 (BCS) GID: DKANXX
MANF: WALTER SARSTEDT

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.450		00.12	02.20	T MOD	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	00009.88	

06068 ACRYLIC SHEET SI60948 STRETCH GID: DUAKXX
MANF: SWEDLOW SPEC: MIL-P-25690A

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	023.8	014.5	0.314			08.80	MOD	No test data	No test data							
X	1	023.8	014.5	0.314		00.11	12.00	T MOD									
X	1	030.0	010.0	0.290		00.13	12.00	T MOD									

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	4.0E-6	1.31	.00			A	A	00020.32	

60264 ACRYLIC TRANSPARENT GID: DKAKXX
MANF: SPEC: MIL-P-13305

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7	0.360		00.03	12.00	T MOD	No test data	No test data							
B	1	024.5	014.3	0.500			09.00	NONE									
X	1	024.5	014.3	0.125		00.10	12.00	T MOD									
X	1	025.9	014.3	0.340		00.05	12.00	T MOD									

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	00208.69	

63506 ACRYLIC TYPE 350S GID: DUAKXX
MANF: SWEDLOW SPEC: MIL-P-25690A

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	00021.76	

Information Handling Services, 2000

62715 ADAPTER CONNECTOR KYNAR/SS GID: BCCTKW
MANF: GLENAIR

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	024.5	014.3				00.60	NONE	No test data		No test data							

66311 ADHESIVE 1 EC1500
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66312 ADHESIVE 1 EC2500
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66313 ADHESIVE 1 EC5
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66314 ADHESIVE 1 EC50
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66315 ADHESIVE 1 EC90
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66316 ADHESIVE 1 MC100
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66317 ADHESIVE 1 MC150
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66318 ADHESIVE 1 MC50
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

67207 ADHESIVE 1099L
MANF: 3M CO.
....NO TEST DATA AVAILABLE....

65922 ADHESIVE 1117
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

65923 ADHESIVE 1137-1
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

65919 ADHESIVE 117
MANF: BASF STRUCTURAL MATERIALS

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	.71	.49	.00	1H-250F-	No test data		

MSFC-HDBK-527 REV F 9999942 0005116 9

Information Handling Services, 2000

67208 ADHESIVE 1300 ROLL COATABLE
MANF: 3M CO
....NO TEST DATA AVAILABLE....

65924 ADHESIVE 1515-1
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

06555 ADHESIVE 17017 A/B POLYURETHANE GID: ABCQXX
MANF: HARTEL ENTERPRISE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.010	0.003	00.50	12.00	T MOD
X	2	025.9	014.3	0.012	0.003	00.00	00.00	NONE
X	1	025.9	014.3	0.012	0.003	00.36	12.00	T MOD
I	1	030.0	010.0	0.020		00.19	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	7.0E-6	3.60	.07	.28	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
B	00023.26	24H-70F- 4H-150F- 24H-70F-

67209 ADHESIVE 1751 B/A
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.75	.06	.00	24H-70F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

67210 ADHESIVE 1838 B/A TAN
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67211 ADHESIVE 1838L B/A TRANSLUCENT
MANF: 3M CO
....NO TEST DATA AVAILABLE....

61700 ADHESIVE 18540 11C/EPON N2 CURE GID: AEERGS
MANF: A D LITTLE
SHELL CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.020			00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00031.00	24H-70F-

67212 ADHESIVE 1870
MANF: 3M CO
....NO TEST DATA AVAILABLE....

20257 ADHESIVE 1872 EPOXY GID: ABBGXX
....NO TEST DATA AVAILABLE....

84942 ADHESIVE 1890
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005117 0

65392 ADHESIVE 1P20025 EPOXY CLASS 1 GID: ABBGXX
MANF: 3M CO

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3				00.00	NONE	No test data		No test data							

66319 ADHESIVE 2 C100
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66320 ADHESIVE 2 C50
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66321 ADHESIVE 2 C500
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

67213 ADHESIVE 2141
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67690 ADHESIVE 2214 HIGH DENSITY
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67691 ADHESIVE 2214 HIGH FLEX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67692 ADHESIVE 2214 NON-METALLIC FIELD
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67214 ADHESIVE 2216 B/A FAST CURE TRANSLUCENT
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67689 ADHESIVE 221N-NI
MANF: 3M CO
....NO TEST DATA AVAILABLE....

05806 ADHESIVE 2223 A/B EPOXY GID: ABBGXX
MANF: FURANE

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	2	023.8	014.5	0.021	0.003	00.00	00.00	NONE	No test data		No test data							
A	1	023.8	014.5	0.021	0.003		05.00	NONE										

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	6.0E-6	1.90	.23	.14	24H-70F-	A	X	00162.36	1H-70F- 1H-150F-

65659 ADHESIVE 286
MANF: ADM TRONICS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005118 2

66322 ADHESIVE 3 CI100
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66323 ADHESIVE 3 CI1000
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66324 ADHESIVE 3 ST1000
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66325 ADHESIVE 3 ST5
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

65925 ADHESIVE 306
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

06581 ADHESIVE 322 EPOXY GID: ABBGXX
MANF: THERMOSET PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.012	0.003		04.70	SMALL
C	1	025.9	014.3	0.008	0.003	00.46	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.5E-6	9.34	2.48	.42	17H-70F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

67217 ADHESIVE 33 RED
MANF: 3M CO
....NO TEST DATA AVAILABLE....

80621 ADHESIVE 330U
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

67218 ADHESIVE 34 NEUTRAL
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67220 ADHESIVE 3501 B/A CLEAR
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.86	.01	.13	16H-46F-
					24H-113F-0psiaVACUUM

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

67221 ADHESIVE 3533 B/A CLEAR
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67222 ADHESIVE 3533 B/A GREY
MANF: 3M CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

67223 ADHESIVE 3570 B/A CLEAR
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67224 ADHESIVE 36 BLACK
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67225 ADHESIVE 37 BLACK SELF EXTINGUISHING
MANF: 3M CO
....NO TEST DATA AVAILABLE....

85370 ADHESIVE 3977-01 THERMAL EPOXY
MANF: MARLOW INDUSTRIES
SPEC: P/M 3977-01

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	%REACT	%TEST
I	1	025.9	014.3	0.007	0.003	00.21	12.00	SMALL	No test data	No test data						

65563 ADHESIVE 3C #202
MANF: 3M CO
....NO TEST DATA AVAILABLE....

65564 ADHESIVE 3C #203
MANF: 3M CO
....NO TEST DATA AVAILABLE....

65560 ADHESIVE 3C #204
MANF: 3M CO
....NO TEST DATA AVAILABLE....

65566 ADHESIVE 3C #27
MANF: 3M CO
....NO TEST DATA AVAILABLE....

65561 ADHESIVE 3C #DW 205
MANF: 3M CO
....NO TEST DATA AVAILABLE....

65565 ADHESIVE 3C HONETCH FOAM
MANF: 3M CO
....NO TEST DATA AVAILABLE....

65562 ADHESIVE 3C PAN-L-BOND
MANF: 3M CO
....NO TEST DATA AVAILABLE....

65567 ADHESIVE 3C STYROBOND
MANF: 3M CO
....NO TEST DATA AVAILABLE....

65568 ADHESIVE 3C WALLBOND
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67227 ADHESIVE 3M AEROSOL 90
MANF: 3M CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005120 0 ■

Information Handling Services, 2000

67228 ADHESIVE 3M AEROSOL SUPER 77H
MANF: 3M CO
....NO TEST DATA AVAILABLE....

84954 ADHESIVE 4-2805
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

84956 ADHESIVE 4-2817
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

20481 ADHESIVE 4144/3496 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

67356 ADHESIVE 4323
MANF: 3M CO
....NO TEST DATA AVAILABLE....

82250 ADHESIVE 444R
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

06046 ADHESIVE 453/EC3917 EPOXY FILM GID: ABBGXX SPEC: MB0120-070T1C1
MANF:
....NO TEST DATA AVAILABLE....

67236 ADHESIVE 4550
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67238 ADHESIVE 4799
MANF: 3M CO
....NO TEST DATA AVAILABLE....

61322 ADHESIVE 4914 ACRYLIC GID: ABAKXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.003		01.60	NONE
A	1	033.0	014.3	0.003	0.003		02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	6.0E-6	1.57	.00		168H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00005.32	168H-70F- 24H-150F-

67241 ADHESIVE 5 GREEN
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67242 ADHESIVE 5 NEUTRAL
MANF: 3M CO
....NO TEST DATA AVAILABLE....

65661 ADHESIVE 501 NEOPRENE
MANF: ADVANCED COATINGS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005121 2 ■

67245 ADHESIVE 5230
MANF: 3M CO
....NO TEST DATA AVAILABLE....

05253 ADHESIVE 5504 EPOXY/AG GID: ABBGXX
MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.27	.03		

ODOR

RT	RT WEIGHT	CURE
No test data		

60151 ADHESIVE 583 GID: ABXXXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

65660 ADHESIVE 626M
MANF: ADM TRONICS
....NO TEST DATA AVAILABLE....

65918 ADHESIVE 6603
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

65921 ADHESIVE 6607
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

69609 ADHESIVE 738/1204 PRIMER
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

67246 ADHESIVE 75
MANF: 3M CO
....NO TEST DATA AVAILABLE....

69629 ADHESIVE 76 RES 6140 (45/55)
MANF: UNION OIL
....NO TEST DATA AVAILABLE....

61963 ADHESIVE 76/KUA FOAM GID: CAXXXX
MANF: 3M CO
CONSOLIDATED KINETIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	1.000		02.45	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60805 ADHESIVE 76/URETHANE FOAM GID: ABDUXX
MANF: 3M CO
CUSTOM PACKING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.010	0.003		01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	V 00003.28	

65920 ADHESIVE 7820/20
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005122 4

66588 ADHESIVE 80
MANF: FLUORO-PLASTICS

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	.00	1.81	.00	24H-302F-0psiaVACUUM	No test data		

67624 ADHESIVE 80X12
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

65675 ADHESIVE 810 OIL/GRIP
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

67247 ADHESIVE 826
MANF: 3M CO
....NO TEST DATA AVAILABLE....

82674 ADHESIVE 828/872/PAPA/EMI-24
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

20449 ADHESIVE 84706
MANF: RAYBESTOS-MANHATTAN
....NO TEST DATA AVAILABLE....

67249 ADHESIVE 847H
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67250 ADHESIVE 847L
MANF: 3M CO
....NO TEST DATA AVAILABLE....

66589 ADHESIVE 85
MANF: FLUORO-PLASTICS
....NO TEST DATA AVAILABLE....

67252 ADHESIVE 880
MANF: 3M CO
....NO TEST DATA AVAILABLE....

82251 ADHESIVE 898C
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

67108 ADHESIVE 910
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67253 ADHESIVE 959
MANF: 3M CO
....NO TEST DATA AVAILABLE....

65934 ADHESIVE 999 CONSTRUCTION
MANF: BEECHAM
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005123 6

Information Handling Services, 2000

05385 ADHESIVE A HMS16-1443 EPOXY GID: BABGXX

MANF: ABLESTIK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.011	0.010	00.00	00.00	NONE
A	1	023.8	014.5	0.011	0.010		04.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.8E-6	2.84	.03		24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00030.27	24H-70F-

67437 ADHESIVE A PRIMER

MANF: TRANSENE

....NO TEST DATA AVAILABLE....

66365 ADHESIVE A R A

MANF: DIMITER EMULSION & CHEMICAL

....NO TEST DATA AVAILABLE....

66424 ADHESIVE A110

MANF: EASTMAN KODAK

....NO TEST DATA AVAILABLE....

66755 ADHESIVE A1216B

MANF: B F GOODRICH

....NO TEST DATA AVAILABLE....

61038 ADHESIVE A1282B EPOXY GID: ABBGXX

MANF: B F GOODRICH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.2E-6	.98	.01	.72	.75H-400F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

66445 ADHESIVE A148

MANF: EASTMAN KODAK

....NO TEST DATA AVAILABLE....

66439 ADHESIVE A167

MANF: EASTMAN KODAK

....NO TEST DATA AVAILABLE....

66426 ADHESIVE A298

MANF: EASTMAN KODAK

....NO TEST DATA AVAILABLE....

66420 ADHESIVE A3

MANF: EASTMAN KODAK

....NO TEST DATA AVAILABLE....

66437 ADHESIVE A32

MANF: EASTMAN KODAK

....NO TEST DATA AVAILABLE....

66421 ADHESIVE A33

MANF: EASTMAN KODAK

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005124 8

66440 ADHESIVE A337
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66441 ADHESIVE A381
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66427 ADHESIVE A383
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66438 ADHESIVE A39
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66422 ADHESIVE A40
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

20092 ADHESIVE A4000 SILICONE GID: ABCKXX
MANF: DOW CORNING

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.34	.70	.00	

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	B	00119.98	72H-70F- 24H-150F-

66423 ADHESIVE A41
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66428 ADHESIVE A43
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66429 ADHESIVE A435
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66430 ADHESIVE A475
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66446 ADHESIVE A517
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66431 ADHESIVE A525
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66432 ADHESIVE A527
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66447 ADHESIVE A528
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005125 T

06341 ADHESIVE A5900 PHENOLIC THERMOSET GID: ABFGXX

MANF: LEAR SIEGLER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.016	0.005		01.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.4E-6	1.76	.00	1.58	9H-350F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

66448 ADHESIVE A596
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66433 ADHESIVE A604
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66434 ADHESIVE A605
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66435 ADHESIVE A620
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66449 ADHESIVE A621
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66450 ADHESIVE A630
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66436 ADHESIVE A8
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

67614 ADHESIVE AA1104
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

65875 ADHESIVE AA1104MB
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

65876 ADHESIVE AA1104RB
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

67620 ADHESIVE AA1106
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

67621 ADHESIVE AA1108
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005126 1 ■

Information Handling Services, 2000

67627 ADHESIVE AA1116
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

67625 ADHESIVE AA1120
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

67615 ADHESIVE AA1122
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

67618 ADHESIVE AA1124
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

67616 ADHESIVE AA1128
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

67617 ADHESIVE AA1130
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

67623 ADHESIVE AA1212
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

67619 ADHESIVE AA1604
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

67622 ADHESIVE AA1612
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

80762 ADHESIVE AA1618
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

67626 ADHESIVE AA2304
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

66606 ADHESIVE AB
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

05648 ADHESIVE ABLEBOND 150-6 EPOXY GID: ABBGXX
MANF: ABLESTIK

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data						A	X	00001.64	24H-70F- 24H-150F-

65569 ADHESIVE ABLEBOND 16-1
MANF: ABLESTIK

MSFC-HDBK-527 REV F 9999942 0005127 3

Information Handling Services, 2000

65569 ADHESIVE ABLEBOND 16-1 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.71	.15	.00	24H-77F- 16H-142F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65570 ADHESIVE ABLEBOND 161-3

MANF: ABLESTIK

....NO TEST DATA AVAILABLE....

65571 ADHESIVE ABLEBOND 163-4

MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.39	.08	.00	2H-170F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65572 ADHESIVE ABLEBOND 184-1

MANF: ABLESTIK

....NO TEST DATA AVAILABLE....

60993 ADHESIVE ABLEBOND 185 EPOXY GID: ABBGXX

MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.08	.01	.00	.5H-332F- 1H-332F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65573 ADHESIVE ABLEBOND 190-3

MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.27	.06	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65574 ADHESIVE ABLEBOND 190-8

MANF: ABLESTIK

....NO TEST DATA AVAILABLE....

69940 ADHESIVE ABLEBOND 204-2

MANF: ABLESTIK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.006	0.010		02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.0E-6	.51	.02	.41	2H-165F-

ODOR

RT	RT WEIGHT	CURE
A	B 3.735	2H-165F-

TOXICITY

65575 ADHESIVE ABLEBOND 224-1

MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.40	.00	.00	1H-126F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05862 ADHESIVE ABLEBOND 293-1 GID: ABBOXX

MANF: ABLESTIK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.023	0.003		03.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005128 5

05862 ADHESIVE ABLEBOND 293-1 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.40	.06	.00	1H-257F-

ODOR

RT	RT	WEIGHT	CURE
X	B	00047.50	3H-165F-

TOXICITY

65576 ADHESIVE ABLEBOND 342-13 ACC
MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.05	.07	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

65577 ADHESIVE ABLEBOND 342-3
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

64219 ADHESIVE ABLEBOND 36-2 EPOXY GID: ABBGXX
MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.83	.01		

ODOR

RT	RT	WEIGHT	CURE
	X	00001.62	

TOXICITY

06131 ADHESIVE ABLEBOND 369-3 CONDUCTIVE GID: ABBGXX
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65578 ADHESIVE ABLEBOND 380-5
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65579 ADHESIVE ABLEBOND 408-3
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

61200 ADHESIVE ABLEBOND 41-1 EPOXY GID: ABBGXX
MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.64	.00	.44	1H-257F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

65580 ADHESIVE ABLEBOND 410-1
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

63987 ADHESIVE ABLEBOND 414-1 GID: ABXXXX
MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	V	00022.93	

TOXICITY

85360 ADHESIVE ABLEBOND 463-1
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

61463 ADHESIVE ABLEBOND 463-1 EPOXY/AG FI11 GID: ABBGMR
MANF: ABLESTIK SPEC: MB0120-081T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.009	0.003	00.59	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005129 7

61463 ADHESIVE ABLEBOND 463-1 EPOXY/AG FI11 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.002	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.002	0.003		04.90	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.62	.01	.00	2H-77F- 1H-142F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00033.83	24H-150F-

TOXICITY

65581 ADHESIVE ABLEBOND 58-1

MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.08	.03	.00	1H-252F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

65582 ADHESIVE ABLEBOND 601-1C

MANF: ABLESTIK

....NO TEST DATA AVAILABLE....

65583 ADHESIVE ABLEBOND 606-2

MANF: ABLESTIK

....NO TEST DATA AVAILABLE....

65584 ADHESIVE ABLEBOND 66-1

MANF: ABLESTIK

....NO TEST DATA AVAILABLE....

65585 ADHESIVE ABLEBOND 681-14

MANF: ABLESTIK

....NO TEST DATA AVAILABLE....

65586 ADHESIVE ABLEBOND 69-5

MANF: ABLESTIK

....NO TEST DATA AVAILABLE....

65587 ADHESIVE ABLEBOND 71-1LMI

MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.57	.01	.00	.5H-212F- .17H-508F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

65588 ADHESIVE ABLEBOND 724-14C

MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	.00	1.81	.00	24H-300F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

80042 ADHESIVE ABLEBOND 731-1 EPOXY GID: ABBGXX

MANF: ABLESTIK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.6	014.5	0.240		00.09	08.20	LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.92	.11	.00	2H-174F-

ODOR

RT	RT	WEIGHT	CURE
	K	22.153	

TOXICITY

MSFC-HDBK-527 REV F 9999942 0005130 3

Information Handling Services, 2000

65589 ADHESIVE ABLEBOND 77-1
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

61324 ADHESIVE ABLEBOND 770-6 EPOXY GID: ABBGXX
MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.60	.00	.00	.75H-300F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

62341 ADHESIVE ABLEBOND 773-2 BRS GID: ABXXXX
MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.24	.00	.24	1H-257F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05356 ADHESIVE ABLEBOND 783-1 EPOXY GID: DPBGXX
MANF: ABLESTIK SPEC: MB0125-062
....NO TEST DATA AVAILABLE....

65590 ADHESIVE ABLEBOND 789-3
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65591 ADHESIVE ABLEBOND 789-4
MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.27	.00	.00	2H-252F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05699 ADHESIVE ABLEBOND 793-3 EPOXY GID: ABBGXX
MANF: ABLESTIK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.015			03.70	NONE
A	1	030.0	010.0	0.006	0.003	00.17	05.90	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	1.18	.00	.86	.5H-302F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00031.69	SEE TEST RPT

65592 ADHESIVE ABLEBOND 826-1
MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.58	.03	.00	.5H-300F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

65593 ADHESIVE ABLEBOND 84-1A
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65594 ADHESIVE ABLEBOND 84-1LMI
MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.31	.00		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

MSFC-HDBK-527 REV F 9999942 0005131 5

Information Handling Services, 2000

80478 ADHESIVE ABLEBOND 84-1LMI S1
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65595 ADHESIVE ABLEBOND 84-3
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65596 ADHESIVE ABLEBOND 843-1
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65597 ADHESIVE ABLEBOND 843-4
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

80479 ADHESIVE ABLEBOND 85-1
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65615 ADHESIVE ABLEBOND 862-7
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65598 ADHESIVE ABLEBOND 868-3
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65599 ADHESIVE ABLEBOND 877-1
MANF: ABLESTIK

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.51	.14	.50	96H-77F- 4H-132F-

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

65600 ADHESIVE ABLEBOND 88-1
MANF: ABLESTIK

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.41	.04	.00	1H-200F-

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

65601 ADHESIVE ABLEBOND 883-1
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65602 ADHESIVE ABLEBOND 883-4
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65603 ADHESIVE ABLEBOND 931-1
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65604 ADHESIVE ABLEBOND 933-1
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005132 7 ■

65605 ADHESIVE ABLEBOND 941-3
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65606 ADHESIVE ABLEBOND 957-2
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

80480 ADHESIVE ABLEBOND 968-2
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

80481 ADHESIVE ABLEBOND 969-1
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65607 ADHESIVE ABLEBOND ECF564A
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

80482 ADHESIVE ABLEBOND SG2001
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

80483 ADHESIVE ABLEBOND SG2002
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

61775 ADHESIVE ABLEFILM 501 GID: BPBGXX
MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.52	.00	.00	.75H-300F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
B	00004.25	SEE TEST RPT

20443 ADHESIVE ABLEFILM 504 EPOXY GID: ABBGXX
MANF: ABLESTIK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.007	0.003		05.50	SMALL
C	1	033.0	014.3	0.007	0.003	00.59	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	7.2E-7	.21	.00		3H-165F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	V 00018.88	3H-165F-

65608 ADHESIVE ABLEFILM 517
MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	00.07	00.01	00.00	3H-165F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

61271 ADHESIVE ABLEFILM 546 KAPTON GID: BPCBXX
MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.94	.03	.00	.17H-199F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

MSFC-HDBK-527 REV F 9999942 0005133 9

Information Handling Services, 2000

05549 ADHESIVE ABLEFILM 550 EPOXY GID: ABBGXX

MANF: ABLESTIK SPEC: MIL-W-81822/3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.005	0.003	10.07	12.00	T NONE
C	1	023.8	014.5	0.005	0.003	01.38	12.00	T NONE
A	1	025.9	014.3	0.029			02.50	NONE
A	1	030.0	009.0	0.008	0.003		03.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.11	.00	.45	4H-302F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	A 00006.99	

65609 ADHESIVE ABLEFILM 550K

MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.11	.00	.00	4H-300F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

06230 ADHESIVE ABLEFILM 551 EPOXY GID: ABBGXX

MANF: ABLESTIK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.010	0.003	00.13	05.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	6.78	.55	1.24	1.5H-329F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 00022.63	

65341 ADHESIVE ABLEFILM 561 GID: ABBGXX

MANF: ABLESTIK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.125			00.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.75	.41	1.30	2H-300F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 00216.30	

65536 ADHESIVE ABLEFILM 561/40% FILLED GID: ABBGXX

MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-6	.41	.01	.11	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

65610 ADHESIVE ABLEFILM 561K

MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.35	.11	.06	2H-257F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

80484 ADHESIVE ABLEFILM 563

MANF: ABLESTIK

....NO TEST DATA AVAILABLE....

80485 ADHESIVE ABLEFILM 563K

MANF: ABLESTIK

....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005134 0

Information Handling Services, 2000

65611 ADHESIVE ABLEFILM 564A
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

80486 ADHESIVE ABLEFILM 564K
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

65612 ADHESIVE ABLEFILM ECF550
MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.22	.03	.00	1H-252F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65613 ADHESIVE ABLEFILM ECF561
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

80487 ADHESIVE ABLEFILM ECF563
MANF: ABLESTIK
....NO TEST DATA AVAILABLE....

05656 ADHESIVE ABLEFOAM 1 EPOXY GID: ABBGXX
MANF: ABLESTIK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.060	0.003		00.50	NONE
X	1	023.8	014.5	0.060	0.003	00.42	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-7	1.87	.01		1H-150F-

ODOR

RT	RT WEIGHT	CURE
	B 00055.06	1H-150F-

TOXICITY

05714 ADHESIVE ABLETHERM 12-1 SILICONE GID: ABCKXX
MANF: ABLESTIK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.009	0.003		00.70	NONE
A	1	030.0	010.0	0.010	0.003	00.10	01.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.35	.08	.00	4H-150F-

ODOR

RT	RT WEIGHT	CURE
A	B 00030.91	2H-165F-

TOXICITY

65614 ADHESIVE ABLETHERM 8-2
MANF: ABLESTIK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.41	.01	.00	12H-77F-
					4H-168F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

81721 ADHESIVE ACCUTHANE UR1100
MANF: H B FULLER
....NO TEST DATA AVAILABLE....

66138 ADHESIVE AD10
MANF: CONAP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005135 2

66139 ADHESIVE AD15
MANF: CONAP
....NO TEST DATA AVAILABLE....

66140 ADHESIVE AD16
MANF: CONAP
....NO TEST DATA AVAILABLE....

66141 ADHESIVE AD3
MANF: CONAP
....NO TEST DATA AVAILABLE....

66142 ADHESIVE AD7
MANF: CONAP
....NO TEST DATA AVAILABLE....

66143 ADHESIVE AD8
MANF: CONAP
....NO TEST DATA AVAILABLE....

66144 ADHESIVE AD9
MANF: CONAP
....NO TEST DATA AVAILABLE....

62716 ADHESIVE ADCAM 760 GID: ABXXXX
MANF: E N MURRAY COMPANY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5			03.32	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00006.96	

60772 ADHESIVE ADIPRENE L100/ALUMINUM OXIDE GID: ABFZXX
MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.24	.03	.00	16H-131F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

05970 ADHESIVE ADX3103.1 EPOXY GID: ABBGBS
MANF: HYSOL/DEXTER SPEC: GA100BK1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.023	0.062	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.7E-6	.14	.00		6H-150F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
B	00089.60	6H-150F-

05474 ADHESIVE ADX3111-1 EPOXY GID: ABBGIA
MANF: HYSOL/DEXTER SPEC: HBO120-105

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.038	0.003	00.00	00.00	NONE
C	1	023.8	014.5	0.038	0.003	00.32	12.00	T NONE
B	2	023.8	014.5	0.008	0.003	00.00	00.00	NONE
B	1	023.8	014.5	0.008	0.003	00.21	06.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.0E-6	.71	.01		2H-180F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
V	00032.07	2H-180F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005136 4

05473 ADHESIVE AE10 EPOXY GID: ABBGXX
MANF: MICRO MEASUREMENTS SPEC: MB0120-084T2

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	2	023.8	014.5	0.001	0.003	00.00	00.00	NONE	No test data		No test data							
A	1	023.8	014.5	0.001	0.003		02.40	NONE										
A	1	023.8	014.5	0.004	0.003		00.00	NONE										
A	1	023.8	014.5	0.005	0.003		02.50	NONE										
A	1	030.0	009.0	0.008	0.003		02.70	SMALL										

THERMAL VACUUM STABILITY						ODOR			TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE	
X	7.8E-7	3.79	.00			A	X	00005.51		

66590 ADHESIVE AF1120
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

67348 ADHESIVE AF126
MANF: 3M CO
....NO TEST DATA AVAILABLE....

60334 ADHESIVE AF126-2-03/06 GID: ABXXXX
MANF: 3M CO

THERMAL VACUUM STABILITY						ODOR			TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE	
C	1.0E-6	2.62	.00	1.34	1.5H-248F-	No test data				

67352 ADHESIVE AF131
MANF: 3M CO
....NO TEST DATA AVAILABLE....

05091 ADHESIVE AF143/EC3917 EPOXY FILM GID: ABBGXX
MANF: 3M CO SPEC: MB0120-070T1C1

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.018	0.003		05.30	SMALL	No test data		No test data							
A	1	030.0	009.0	0.010	0.003		04.30	SMALL										
B	1	033.0	014.3	0.018	0.003	00.15	10.50	NONE										

THERMAL VACUUM STABILITY						ODOR			TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE	
C	1.0E-6	1.89	.02	.00	1H-347F-0psiaVACUUM	A	A	00030.97		

67353 ADHESIVE AF30
MANF: 3M CO

THERMAL VACUUM STABILITY						ODOR			TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE	
B	1.0E-6	.88	.01	.00	2H-351F-	No test data				

05104 ADHESIVE AF3002 EPOXY FILM GID: ABBGXX
MANF: 3M CO

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	023.8	014.5	0.068		00.16	12.00	T SMALL	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR			TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE	
C	1.0E-6	.94	.12	.00	16H-250F-	A	K	00115.82		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005137 6

60336 ADHESIVE AF3015 GID: ABXXXX
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.38	.00	.00	1H-270F- 2H-351F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

67351 ADHESIVE AF3024
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.57	.22	.96	1H-248F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

67354 ADHESIVE AF31
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	2.34	.33	.00	1H-347F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05225 ADHESIVE AF42 EPOXY FILM GID: ACBGXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.006	0.003		02.80	NONE
A	1	030.0	010.0	0.006	0.010		00.90	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.91	.37	.00	1H-351F- 1H-341F-

ODOR

RT	RT WEIGHT	CURE
A	X 00010.35	24H-350F-50psiaRAISE TEMP. TO 350F/ @10F PER MINUTE. 24H-350F-50psia

TOXICITY

60843 ADHESIVE AF770 GID: ABCQXX
MANF: UBS CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.3E-6	2.69	.03		1H-70F- 72H-70F-

ODOR

RT	RT WEIGHT	CURE
A	X 00005.00	1H-70F- 72H-70F-

TOXICITY

65893 ADHESIVE ALLABOND 20/20
MANF: BACON
....NO TEST DATA AVAILABLE....

61199 ADHESIVE AMICON 845 EPOXY GID: ABBGXX
MANF: AMICON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.64	.00	.32	1H-300F- 1H-302F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65699 ADHESIVE AMICON A329-1
MANF: AMICON
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

65700 ADHESIVE AMICON C110
MANF: AMICON

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.81	.95	.00	1H-302F-	No test data		

65701 ADHESIVE AMICON C115
MANF: AMICON
....NO TEST DATA AVAILABLE....

65702 ADHESIVE AMICON C120
MANF: AMICON
....NO TEST DATA AVAILABLE....

65708 ADHESIVE AMICON C770-4
MANF: AMICON
....NO TEST DATA AVAILABLE....

65709 ADHESIVE AMICON C770-5
MANF: AMICON
....NO TEST DATA AVAILABLE....

65710 ADHESIVE AMICON C805
MANF: AMICON
....NO TEST DATA AVAILABLE....

65721 ADHESIVE AMICON C840
MANF: AMICON
....NO TEST DATA AVAILABLE....

61198 ADHESIVE AMICON C840-23 EPOXY GID: ABBGXX
MANF: AMICON

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.61	.00	.00	1H-257F-	No test data		

65711 ADHESIVE AMICON C850-16
MANF: AMICON
....NO TEST DATA AVAILABLE....

65712 ADHESIVE AMICON C850-5
MANF: AMICON
....NO TEST DATA AVAILABLE....

65713 ADHESIVE AMICON C850-5A
MANF: AMICON
....NO TEST DATA AVAILABLE....

65714 ADHESIVE AMICON C850-6
MANF: AMICON
....NO TEST DATA AVAILABLE....

65715 ADHESIVE AMICON C868-1
MANF: AMICON
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005139 T ■

Information Handling Services, 2000

65703 ADHESIVE AMICON C928-46
MANF: AMICON
....NO TEST DATA AVAILABLE....

65716 ADHESIVE AMICON C929-72-9
MANF: AMICON
....NO TEST DATA AVAILABLE....

65717 ADHESIVE AMICON C930-55-2
MANF: AMICON
....NO TEST DATA AVAILABLE....

65718 ADHESIVE AMICON C932-46
MANF: AMICON
....NO TEST DATA AVAILABLE....

65719 ADHESIVE AMICON C932-62-1
MANF: AMICON
....NO TEST DATA AVAILABLE....

65720 ADHESIVE AMICON C940-7
MANF: AMICON
....NO TEST DATA AVAILABLE....

65704 ADHESIVE AMICON CS489
MANF: AMICON
....NO TEST DATA AVAILABLE....

65705 ADHESIVE AMICON CS489-2
MANF: AMICON
....NO TEST DATA AVAILABLE....

65722 ADHESIVE AMICON G843
MANF: AMICON
....NO TEST DATA AVAILABLE....

65723 ADHESIVE AMICON ME5146
MANF: AMICON
....NO TEST DATA AVAILABLE....

65724 ADHESIVE AMICON ME778-6
MANF: AMICON
....NO TEST DATA AVAILABLE....

65725 ADHESIVE AMICON ME785
MANF: AMICON
....NO TEST DATA AVAILABLE....

65726 ADHESIVE AMICON ME845-3
MANF: AMICON

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	00.30	00.01	00.00	1H-258F- 1H-252F-	No test data		-

65727 ADHESIVE AMICON ME855-2
MANF: AMICON
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005140 6

Information Handling Services, 2000

65728 ADHESIVE AMICON ME865-1
MANF: AMICON
....NO TEST DATA AVAILABLE....

65729 ADHESIVE AMICON ME868-2
MANF: AMICON
....NO TEST DATA AVAILABLE....

65730 ADHESIVE AMICON ME930-12-4
MANF: AMICON
....NO TEST DATA AVAILABLE....

65731 ADHESIVE AMICON ME932-44
MANF: AMICON
....NO TEST DATA AVAILABLE....

65732 ADHESIVE AMICON SC110
MANF: AMICON
....NO TEST DATA AVAILABLE....

65733 ADHESIVE AMICON SC130
MANF: AMICON
....NO TEST DATA AVAILABLE....

65734 ADHESIVE AMICON SC130-3
MANF: AMICON
....NO TEST DATA AVAILABLE....

65735 ADHESIVE AMICON SC17
MANF: AMICON
....NO TEST DATA AVAILABLE....

65790 ADHESIVE AMICON SLC C860-2
MANF: AMICON
....NO TEST DATA AVAILABLE....

65706 ADHESIVE AMICON T1206
MANF: AMICON
....NO TEST DATA AVAILABLE....

65707 ADHESIVE AMICON T426
MANF: AMICON
....NO TEST DATA AVAILABLE....

65736 ADHESIVE AMICON TG86
MANF: AMICON
....NO TEST DATA AVAILABLE....

65737 ADHESIVE AMICON TG86EC
MANF: AMICON
....NO TEST DATA AVAILABLE....

65738 ADHESIVE AMICON TG86TC
MANF: AMICON
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005141 8

Information Handling Services, 2000

62445 ADHESIVE AMICON XT1369 A/B GID: ABXXXX
MANF: AMICON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.008	0.003		00.40	SMALL
C	1	030.0	010.0	0.008	0.003	00.30	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.2E-6	3.38	.00	.13	96H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00021.86	96H-70F-

20197 ADHESIVE AMPHENOL 912 EPOXY/PHENOL GID: ABBGXX
....NO TEST DATA AVAILABLE....

62235 ADHESIVE AMSCO HOT MELT 112 GID: ABCDXX
MANF: UNION OIL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.061			08.80	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.5E-6	15.18	8.30	.03	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00022.12	

62236 ADHESIVE AMSCO HOT MELT 233 GID: ABCDXX
MANF: UNION OIL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.061			05.00	MOD
X	1	033.0	014.3	0.060		00.24	07.20	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.5E-6	5.32	1.91	.02	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00022.74	

60283 ADHESIVE AMSCO HOT MELT 344
MANF: UNION OIL
....NO TEST DATA AVAILABLE....

67474 ADHESIVE AMSCO RES 19BR64
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67470 ADHESIVE AMSCO RES 19RB64P
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67439 ADHESIVE AMSCO RES 202A
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67477 ADHESIVE AMSCO RES 202AH
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67478 ADHESIVE AMSCO RES 202AM
MANF: UNION 76
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005142 T

67438 ADHESIVE AMSCO RES 3001
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67441 ADHESIVE AMSCO RES 3001P
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67475 ADHESIVE AMSCO RES 3004
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67440 ADHESIVE AMSCO RES 3008
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67442 ADHESIVE AMSCO RES 3034
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67443 ADHESIVE AMSCO RES 3063
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67444 ADHESIVE AMSCO RES 3151
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67445 ADHESIVE AMSCO RES 4000
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67502 ADHESIVE AMSCO RES 4000 (50/50)
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67503 ADHESIVE AMSCO RES 4001
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67446 ADHESIVE AMSCO RES 4040
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67447 ADHESIVE AMSCO RES 4072
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67448 ADHESIVE AMSCO RES 4104 (65/35)
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67479 ADHESIVE AMSCO RES 5007
MANF: UNION 76
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005143 1

67450 ADHESIVE AMSCO RES 528
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67451 ADHESIVE AMSCO RES 542
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67452 ADHESIVE AMSCO RES 546
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67498 ADHESIVE AMSCO RES 6038
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67501 ADHESIVE AMSCO RES 6105 (45/55)
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67449 ADHESIVE AMSCO RES 6130 (HS/SS)
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67499 ADHESIVE AMSCO RES 6150 (45/55)
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67471 ADHESIVE AMSCO RES 6206
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67473 ADHESIVE AMSCO RES 6213
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67487 ADHESIVE AMSCO RES 6221
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67495 ADHESIVE AMSCO RES 6222
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67496 ADHESIVE AMSCO RES 6247
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67483 ADHESIVE AMSCO RES 6255
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67492 ADHESIVE AMSCO RES 6272
MANF: UNION 76
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005144 3 ■

67457 ADHESIVE AMSCO RES 7200
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67458 ADHESIVE AMSCO RES 8795
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67459 ADHESIVE AMSCO RES 9000
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67460 ADHESIVE AMSCO RES 9001
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67461 ADHESIVE AMSCO RES 9102
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67462 ADHESIVE AMSCO RES 9105
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67463 ADHESIVE AMSCO RES 9201
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67464 ADHESIVE AMSCO RES 9202
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67465 ADHESIVE AMSCO RES 9202V60
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67466 ADHESIVE AMSCO RES 9204
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67488 ADHESIVE AMSCO RES 9205
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67467 ADHESIVE AMSCO RES 9211
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67468 ADHESIVE AMSCO RES 9213
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67484 ADHESIVE AMSCO RES 9214
MANF: UNION 76
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005145 5

Information Handling Services, 2000

67469 ADHESIVE AMSCO RES 9218
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67453 ADHESIVE AMSCO RES 930
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67454 ADHESIVE AMSCO RES 931
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67455 ADHESIVE AMSCO RES 940
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67485 ADHESIVE AMSCO RES 9621
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67486 ADHESIVE AMSCO RES 9622
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67456 ADHESIVE AMSCO RES M3153
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67505 ADHESIVE AMSCO RES P528F
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67506 ADHESIVE AMSCO RES P546
MANF: UNION 76
....NO TEST DATA AVAILABLE....

67480 ADHESIVE AMSCO RES S55
MANF: UNION 76
....NO TEST DATA AVAILABLE....

66723 ADHESIVE AP138 ALL IN ONE
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66724 ADHESIVE AP139 ALL IN ONE
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

65662 ADHESIVE AP1400
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

65663 ADHESIVE AP2108
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005146 7

Information Handling Services, 2000

65664 ADHESIVE AP2110
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

65665 ADHESIVE AP2118 HI-TEMP
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

65666 ADHESIVE AP2120 HI-TEMP
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

65667 ADHESIVE AP2400 QUICK SET
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

65668 ADHESIVE AP2410 QUICK SET
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67595 ADHESIVE AQUAFORTE 108W
MANF: ADM TRONICS
....NO TEST DATA AVAILABLE....

66591 ADHESIVE AR1004
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81690 ADHESIVE AR1005
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81691 ADHESIVE AR1009
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

66592 ADHESIVE AR1100
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

66593 ADHESIVE AR1130
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81692 ADHESIVE AR1150
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

66594 ADHESIVE AR1218
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

66595 ADHESIVE AR1418
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005147 9

Information Handling Services, 2000

66596 ADHESIVE AR1650
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

66597 ADHESIVE AR1700
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81693 ADHESIVE AR1776
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81694 ADHESIVE AR1930FR
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

20459 ADHESIVE ARALDITE 101 GID: ABXXXX
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84507 ADHESIVE ARALDITE 1138/HY906/DY062
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

60363 ADHESIVE ARALDITE 138/HV998 GID: ABXXXX
MANF: CIBA-GEIGY

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
B	1.0E-6	.74	.03	.51	16H-46F- 72H-176F- 8H-212F- 312H-176F-		K	00002.17	

68027 ADHESIVE ARALDITE 465 A80
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66085 ADHESIVE ARALDITE 465A-80-1
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66086 ADHESIVE ARALDITE 465A-80-2
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66109 ADHESIVE ARALDITE 502
MANF: CIBA-GEIGY

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	1.0E-6	2.00	.02	.00	1H-70F- 6H-120F-	No test data			

66087 ADHESIVE ARALDITE 506
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005148 0

Information Handling Services, 2000

66088 ADHESIVE ARALDITE 507-1
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66089 ADHESIVE ARALDITE 507-2
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66090 ADHESIVE ARALDITE 507-3
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66091 ADHESIVE ARALDITE 507-4
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66092 ADHESIVE ARALDITE 509
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66093 ADHESIVE ARALDITE 6004-1
MANF: CIBA-GEIGY

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.74	.07	.00	4H-70F- 5H-140F-

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

66094 ADHESIVE ARALDITE 6004-2
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

06282 ADHESIVE ARALDITE 6005/906 GID: ABXXXX
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84508 ADHESIVE ARALDITE 6010/AROMATIC DIAMINE
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84510 ADHESIVE ARALDITE 6010/DICY
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84512 ADHESIVE ARALDITE 6010/HY940/EHT939
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84514 ADHESIVE ARALDITE 6010/POLYAMIDE
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84515 ADHESIVE ARALDITE 6010/TETA
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66095 ADHESIVE ARALDITE 6020-1
MANF: CIBA-GEIGY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005149 2

66096 ADHESIVE ARALDITE 6020-2
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66097 ADHESIVE ARALDITE 6020-3
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66098 ADHESIVE ARALDITE 6060-1
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66099 ADHESIVE ARALDITE 6060-2
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66100 ADHESIVE ARALDITE 6060-3
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84517 ADHESIVE ARALDITE 7071/DICY
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84520 ADHESIVE ARALDITE 7071/POLYAMIDE
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

60428 ADHESIVE ARALDITE AV100 GID: ABXXXX
MANF: CIBA-GEIGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	1.92	.08	1.58	24H-140F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66102 ADHESIVE ARALDITE CY8043-2
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66103 ADHESIVE ARALDITE DY027-3
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84524 ADHESIVE ARALDITE EPN1138/BR3MEA
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84526 ADHESIVE ARALDITE EPN1138/HT972
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84527 ADHESIVE ARALDITE EPN1138/HY907/DY062
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

69833 ADHESIVE ARALDITE EPN1138/NADIC METHYL ANHYDRIDE N/N-DIMETHYL BENZYLAMIN GID: ABXXXX
MANF: CIBA-GEIGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
	5.0E-6	.70	.01	.56	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005150 9

66104 ADHESIVE ARALDITE GY005-3
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66105 ADHESIVE ARALDITE GY6005-1
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66106 ADHESIVE ARALDITE GY6005-2
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66107 ADHESIVE ARALDITE GY6005-3
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66108 ADHESIVE ARALDITE GY6005-4
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84530 ADHESIVE ARALDITE MY720/HY906/FORM VAR 7/70
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84645 ADHESIVE ARALDITE MY720/HY972/FORM VAR 7/70
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66084 ADHESIVE ARALDITE RP138
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

65794 ADHESIVE AREMCOBOND 515
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

61376 ADHESIVE AREMCOBOND 517 EPOXY GID: ABBGXX
MANF: AREMCO PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.010	0.003	00.10	10.50	SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.7E-6	1.28	.06		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00053.14	24H-70F-

65795 ADHESIVE AREMCOBOND 525
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

65796 ADHESIVE AREMCOBOND 526
MANF: AREMCO PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	030.0	010.0	0.005	0.003	00.00	00.00	NONE
B	1	030.0	010.0	0.005	0.003	01.00	09.00	SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR

RT

TOXICITY

RT	WEIGHT	CURE

MSFC-HDBK-527 REV F 9999942 0005151 0

Information Handling Services, 2000

65796 ADHESIVE AREMCOBOND 526 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					2H-200F-
					16H-325F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
		2H-200F-
		16H-326F-

80743 ADHESIVE AREMCOBOND 529
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

65797 ADHESIVE AREMCOBOND 556
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

65798 ADHESIVE AREMCOBOND 561
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

65799 ADHESIVE AREMCOBOND 568
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

65800 ADHESIVE AREMCOBOND 570
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

63016 ADHESIVE ARMAFLEX BLACK GID: DOXXXX
MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7				01.30	NONE
I	1	024.5	014.5			00.65	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20711 ADHESIVE ARMSTRONG 520 NEOPRENE GID: ABDBXX
MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		00.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00001.90	168H-70F-

65842 ADHESIVE ARMSTRONG 529
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

60195 ADHESIVE ARMSTRONG A12 EPOXY GID: AEBJXX
MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.005	0.003	00.00	00.00	NONE
B	1	020.9	014.7	0.005	0.003	00.34	05.40	NONE
I	1	030.0	009.0	0.006	0.003	00.27	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.62	.02	.00	2H-185F-
					48H-125F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005152 2

65811 ADHESIVE ARMSTRONG A12-2
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65812 ADHESIVE ARMSTRONG A12-3
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65813 ADHESIVE ARMSTRONG A12/T
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

05308 ADHESIVE ARMSTRONG A18 EPOXY PASTE GID: ABXXXX
MANF: ARMSTRONG

FLAMMABILITY										FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	023.8	014.5	0.006	0.003	00.50	07.00	T NONE	No test data		No test data							

65814 ADHESIVE ARMSTRONG A2/A
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

63454 ADHESIVE ARMSTRONG A2/E GID: ABBGXX
MANF: ARMSTRONG

FLAMMABILITY										FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	030.0	010.0	0.010	0.010	00.13	07.03	MOD	No test data		No test data							

65815 ADHESIVE ARMSTRONG A2/H20
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65816 ADHESIVE ARMSTRONG A2/W
MANF: ARMSTRONG

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.44	.00	.00	.75H-165F- .75H-230F-	No test data		

65817 ADHESIVE ARMSTRONG A271
MANF: ARMSTRONG

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.50	.02	.00		No test data		

62717 ADHESIVE ARMSTRONG A3 GID: ABBGXX
MANF: ARMSTRONG

FLAMMABILITY										FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	025.9	014.3	0.007	0.003	00.40	12.00	T NONE	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.9E-6	1.40	.27	.27		A	00015.90	

65818 ADHESIVE ARMSTRONG A3/A
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005153 4

65819 ADHESIVE ARMSTRONG A3/E

MANF: ARMSTRONG

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.85	.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65820 ADHESIVE ARMSTRONG A31 GID: ABBGXX

MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	030.0	010.0	0.010	0.003	00.00	00.00	NONE
B	1	030.0	010.0	0.010	0.003	01.20	09.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.74	.01	.00	168H-70F-

ODOR

RT	RT WEIGHT	CURE
A	K 21.655	

TOXICITY

65821 ADHESIVE ARMSTRONG A36

MANF: ARMSTRONG

....NO TEST DATA AVAILABLE....

65822 ADHESIVE ARMSTRONG A39

MANF: ARMSTRONG

....NO TEST DATA AVAILABLE....

65823 ADHESIVE ARMSTRONG A40

MANF: ARMSTRONG

....NO TEST DATA AVAILABLE....

20355 ADHESIVE ARMSTRONG A5-4318/H3486 EPOXY GID: ABBGXX

MANF: ARMSTRONG
HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.68	.28	.00	.5H-111F- 4H-302F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65824 ADHESIVE ARMSTRONG A6/A

MANF: ARMSTRONG

....NO TEST DATA AVAILABLE....

65825 ADHESIVE ARMSTRONG A6/E

MANF: ARMSTRONG

....NO TEST DATA AVAILABLE....

65826 ADHESIVE ARMSTRONG A6/H20

MANF: ARMSTRONG

....NO TEST DATA AVAILABLE....

65827 ADHESIVE ARMSTRONG A66

MANF: ARMSTRONG

....NO TEST DATA AVAILABLE....

20273 ADHESIVE ARMSTRONG A7-4322 GID: ABXXXX

MANF: ARMSTRONG
HYSOL/DEXTER

....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005154 6

Information Handling Services, 2000

05492 ADHESIVE ARMSTRONG A701 EPOXY GID: ABBGXX

MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.010	0.003		11.80	NONE
A	1	023.8	014.5	0.023			03.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00038.77	2H-350F-

65830 ADHESIVE ARMSTRONG A702

MANF: ARMSTRONG

....NO TEST DATA AVAILABLE....

65828 ADHESIVE ARMSTRONG A706

MANF: ARMSTRONG

....NO TEST DATA AVAILABLE....

65829 ADHESIVE ARMSTRONG A708

MANF: ARMSTRONG

....NO TEST DATA AVAILABLE....

20712 ADHESIVE ARMSTRONG A8-4219/H2-3404 EPOXY GID: ABBGGS

MANF: ARMSTRONG SPEC: T0811/A0429
HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.004	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.004	0.003	00.47	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.17	3.40	.00	168H-70F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
B	00019.21	168H-70F-

06424 ADHESIVE ARMSTRONG A875 NITRILE RUBBER GID: ABXXXX

MANF: ARMSTRONG

....NO TEST DATA AVAILABLE....

61368 ADHESIVE ARMSTRONG ACTA 1 RESIN GID: ABBGXX

MANF: ARMSTRONG

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00016.03	

60369 ADHESIVE ARMSTRONG C1 EPOXY GID: ABBGXX

MANF: ARMSTRONG SPEC: MIL-I-43553

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.004	0.004		02.00	NONE
A	1	030.0	010.0	0.004	0.004		02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.42	.06	.00	8H-149F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

65831 ADHESIVE ARMSTRONG C1/A

MANF: ARMSTRONG

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005155 8

65832 ADHESIVE ARMSTRONG C1/E
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

60587 ADHESIVE ARMSTRONG C2/A EPOXY GID: AEBGXX
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65833 ADHESIVE ARMSTRONG C3/A
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65834 ADHESIVE ARMSTRONG C3/E
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65837 ADHESIVE ARMSTRONG C4/D
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65835 ADHESIVE ARMSTRONG C4/W
MANF: ARMSTRONG

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.89	.28	.00	168H-70F-	No test data		

65838 ADHESIVE ARMSTRONG C7/H20
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

06530 ADHESIVE ARMSTRONG C7/W EPOXY GID: ABBGXX
MANF: ARMSTRONG

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	00.36	00.02	00.00	504H-70F-	No test data		

65839 ADHESIVE ARMSTRONG C7/W1
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65840 ADHESIVE ARMSTRONG C7/W2
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65841 ADHESIVE ARMSTRONG C7/W3
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65843 ADHESIVE ARMSTRONG D218 INDUSTRIAL
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65844 ADHESIVE ARMSTRONG D222 INDUSTRIAL
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005156 T

65845 ADHESIVE ARMSTRONG D234 CONTACT
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65846 ADHESIVE ARMSTRONG D283 INDUSTRIAL
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65847 ADHESIVE ARMSTRONG D284
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65848 ADHESIVE ARMSTRONG D500 CONTACT
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65849 ADHESIVE ARMSTRONG F1450 PANEL AND WALLBOARD
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

20103 ADHESIVE ARMSTRONG J1162 RESIN BASED GID: ABXXXX
MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.004	0.003		03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.01	.00	.00	1.67H-156F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65851 ADHESIVE ARMSTRONG J1177 GREY
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65852 ADHESIVE ARMSTRONG J1188 INDUSTRIAL
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65853 ADHESIVE ARMSTRONG J1199 TP INDUSTRIAL PART A
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65854 ADHESIVE ARMSTRONG J1199 TP INDUSTRIAL PART B
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65855 ADHESIVE ARMSTRONG N111 INDUSTRIAL
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65856 ADHESIVE ARMSTRONG N117 INDUSTRIAL
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65857 ADHESIVE ARMSTRONG N122
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005157 1

65858 ADHESIVE ARMSTRONG S1200 CONTACT
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65859 ADHESIVE ARMSTRONG S139 TILE-ON
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65860 ADHESIVE ARMSTRONG S140 GLAZECRAFT WALLTILE
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65861 ADHESIVE ARMSTRONG S200 A/B
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65862 ADHESIVE ARMSTRONG S235 MULTIPURPOSE
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65863 ADHESIVE ARMSTRONG S252 PAVIMAR
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65864 ADHESIVE ARMSTRONG S280
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65865 ADHESIVE ARMSTRONG S285 WALLBASE
MANF: ARMSTRONG

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.56	.16	.00	2H-356F-0psiaVACUUM	No test data		

65866 ADHESIVE ARMSTRONG S553 SEAMSEALING
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65867 ADHESIVE ARMSTRONG S580
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65868 ADHESIVE ARMSTRONG S665 TROWELABLE INTERFLEX
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65869 ADHESIVE ARMSTRONG S670 LATEX INTERFLEX
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65870 ADHESIVE ARMSTRONG S700 TILE BRUSH-ON
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65871 ADHESIVE ARMSTRONG S750 TILE ROLL-ON
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005158 3

65872 ADHESIVE ARMSTRONG S821 SEAMSEALING
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65873 ADHESIVE ARMSTRONG S89 TILE
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65874 ADHESIVE ARMSTRONG S90 TILE
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

05864 ADHESIVE ARMSTRONG X81/A EPOXY GID: ABBGXX
MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005	0.003		03.40	SMALL
A	1	023.8	014.5	0.006	0.003		03.30	SMALL
A	1	023.8	014.5	0.008	0.003		02.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	1.84	.01	1.48	24H-70F- 2H-167F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65836 ADHESIVE ARMSTRONG X81/E
MANF: ARMSTRONG
....NO TEST DATA AVAILABLE....

65407 ADHESIVE ARON ALPHA 202 GID: ABXXXX
MANF: TOAGOSEI CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80763 ADHESIVE AROPOL 7240
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

65877 ADHESIVE AROSET 1044Z40
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

65878 ADHESIVE AROSET 1051Z45
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

65879 ADHESIVE AROSET 1081Z45
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

65880 ADHESIVE AROSET 1214C30
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

65881 ADHESIVE AROSET 1612Z35
MANF: ASHLAND CHEM

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005159 5

65882 ADHESIVE AROSET 1832Z1-35
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

65883 ADHESIVE AROSET 1857Z34
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

65884 ADHESIVE AROSET 1910TH52
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

65885 ADHESIVE AROSET 2020W50
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

67630 ADHESIVE AROSET 2022W50
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

67631 ADHESIVE AROSET 2201W50
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

67632 ADHESIVE AROSET 2202W50
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

67633 ADHESIVE AROSET 2301W50
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

67634 ADHESIVE AROSET 2302W50
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

67635 ADHESIVE AROSET 2431W50
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

65886 ADHESIVE AROSET 2510W62
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

65887 ADHESIVE AROSET 2520W60
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

67636 ADHESIVE AROSET 2532W50
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

66607 ADHESIVE AS
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005160 1

Information Handling Services, 2000

66608 ADHESIVE ASSEMBLY GLUE 160
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66609 ADHESIVE ASSEMBLY GLUE 65
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66610 ADHESIVE ASSEMBLY GLUE 70A
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66611 ADHESIVE ASSEMBLY GLUE 8
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66612 ADHESIVE ASSEMBLY GLUE 8 PLUS 5%
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66613 ADHESIVE ASSEMBLY GLUE HIGH TACK
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66614 ADHESIVE ASSEMBLY GLUE T2A
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66615 ADHESIVE ASSEMBLY GLUE TX BROWN
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66976 ADHESIVE ASSURE ELECTRICAL TYPE RETAINER
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

66977 ADHESIVE ASSURE ELECTRICAL TYPE THREADLOCKER
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

66978 ADHESIVE ASSURE SURFACE CURING THREADLOCKER
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

85368 ADHESIVE AVIMID N COMPOSITE GID: ABXXXX
MANF: DUPONT SPEC: P/N 5772-50
....NO TEST DATA AVAILABLE....

00145 ADHESIVE AZ/CAT E EPOXY GID: ABAZBG
....NO TEST DATA AVAILABLE....

63724 ADHESIVE BACON FA8-BA5 COATED WITH SCOTCHCAST 280 B/A GID: ABBGXX
MANF: 3M CO
BACON

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT %	CURE
							00010.37	

MSFC-HDBK-527 REV F 9999942 0005161 3

Information Handling Services, 2000

80837 ADHESIVE BACON K31
MANF: BACON
....NO TEST DATA AVAILABLE....

80838 ADHESIVE BACON K50
MANF: BACON
....NO TEST DATA AVAILABLE....

80839 ADHESIVE BACON K5235
MANF: BACON
....NO TEST DATA AVAILABLE....

60156 ADHESIVE BAP 1 PHENOL FORMALDEHYD GID: ABXXXX
....NO TEST DATA AVAILABLE....

67641 ADHESIVE BETAMATE 435.71
MANF: ESSEX CHEM CORP
....NO TEST DATA AVAILABLE....

67642 ADHESIVE BETAMATE 435.72
MANF: ESSEX CHEM CORP
....NO TEST DATA AVAILABLE....

67643 ADHESIVE BETAMATE 435.81
MANF: ESSEX CHEM CORP
....NO TEST DATA AVAILABLE....

66520 ADHESIVE BETAMATE 57.511/57.512 STRUCTURAL
MANF: ESSEX CHEM CORP
....NO TEST DATA AVAILABLE....

66519 ADHESIVE BETAMATE 57.541/57.542 STRUCTURAL
MANF: ESSEX CHEM CORP
....NO TEST DATA AVAILABLE....

81476 ADHESIVE BETASEAL 20-601
MANF: ESSEX CHEM CORP
....NO TEST DATA AVAILABLE....

81477 ADHESIVE BETASEAL 550.02
MANF: ESSEX CHEM CORP
....NO TEST DATA AVAILABLE....

81479 ADHESIVE BETASEAL 551.02
MANF: ESSEX CHEM CORP
....NO TEST DATA AVAILABLE....

81478 ADHESIVE BETASEAL 553.02
MANF: ESSEX CHEM CORP
....NO TEST DATA AVAILABLE....

81480 ADHESIVE BETASEAL XP01543C
MANF: ESSEX CHEM CORP
....NO TEST DATA AVAILABLE....

65530 ADHESIVE BIPAX TRADUCT BB2902 GID: ABBGXX
MANF: TRA-CON INC

MSFC-HDBK-527 REV F 9999942 0005162 5

Information Handling Services, 2000

65530 ADHESIVE BIPAX TRADUCT BB2902 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.010	0.003	0.76	11.80	NONE
A	1	025.9	014.3	0.010	0.003		05.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.07	.04	.00	2H-140F-

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	B	00010.26	24H-70F-
			24H-150F-

81119 ADHESIVE BLACK MAGIC

MANF: MASTER BOND

....NO TEST DATA AVAILABLE....

60317 ADHESIVE BONDING 6035 GID: ABXXXX

MANF: PALMER IND

....NO TEST DATA AVAILABLE....

80242 ADHESIVE BONDING LM52 T46 GID: ABXXXX

MANF: LEFCO WELD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.120		0.1	12.00	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.35	.19	.00	

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	A	69.418	

67093 ADHESIVE BONDMASTER 4500+

MANF: NATIONAL STARCH AND CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.72	.13	.00	6H-200F-

ODOR

RT
No test data

TOXICITY

RT	RT	WEIGHT	CURE

06152 ADHESIVE BONDMASTER 81-0590 GID: ABXXXX

MANF: NATIONAL STARCH AND CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	016.5	0.007	0.003	02.38	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.6E-7	2.72	.13		168H-70F-

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
	V	00011.38	168H-70F-

20104 ADHESIVE BONDMASTER E645 GID: ABBGXX

MANF: NATIONAL STARCH AND CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005	0.003		02.80	NONE
A	1	030.0	009.0	0.005	0.003		04.20	SMALL
B	1	035.0	009.0	0.005	0.003		06.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.68	.04	.00	1H-400F-

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
	B	00020.87	14H-266F-

60795 ADHESIVE BONDMASTER G781 GID: ABHDXX

MANF: NATIONAL STARCH AND CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005163 7

60795 ADHESIVE BONDMASTER G781 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		02.00	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.0E-7	2.64	.19		

ODOR

RT
X

TOXICITY

RT	RT WEIGHT	CURE
X	00002.58	72H-70F-

67559 ADHESIVE BONDMASTER M606

MANF: NATIONAL STARCH AND CHEMICAL

....NO TEST DATA AVAILABLE....

67095 ADHESIVE BONDMASTER M620

MANF: NATIONAL STARCH AND CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.75	.03	.00	2H-175F- 1H-300F- 2H-392F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

67097 ADHESIVE BONDMASTER M666

MANF: NATIONAL STARCH AND CHEMICAL

....NO TEST DATA AVAILABLE....

67094 ADHESIVE BONDMASTER M688 CH16

MANF: NATIONAL STARCH AND CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.02	.21	.00	24H-120F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

67096 ADHESIVE BONDMASTER M688 CH8

MANF: NATIONAL STARCH AND CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.91	.11	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

20171 ADHESIVE BONDMASTER M777 A/B EPOXY GID: AEBMXX

MANF: NATIONAL STARCH AND CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.026	0.003	00.00	00.00	NONE
B	1	023.8	014.5	0.026	0.003		09.30	SMALL
I	1	030.0	010.0	0.039		00.20	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.41	.14	.00	8H-150F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
V	00046.70	168H-70F-

65960 ADHESIVE BOSTIK 1007

MANF: BOSTIK FINCH

....NO TEST DATA AVAILABLE....

60382 ADHESIVE BOSTIK 1008 GID: ABXXXX

MANF: BOSTIK FINCH SPEC: USBI99600-0002

....NO TEST DATA AVAILABLE....

69803 ADHESIVE BOSTIK 1009A/1008B

MANF: BOSTIK FINCH

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005164 9

65961 ADHESIVE BOSTIK 1015
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65962 ADHESIVE BOSTIK 1076
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65963 ADHESIVE BOSTIK 1096
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65964 ADHESIVE BOSTIK 1101
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65965 ADHESIVE BOSTIK 1142
MANF: BOSTIK FINCH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.44	.36	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65966 ADHESIVE BOSTIK 1205
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

20499 ADHESIVE BOSTIK 1205/B9072 GID: ABXXXX
MANF: BOSTIK FINCH SPEC: ST30A685-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.005	0.003		02.60	NONE
A	1	033.0	014.3	0.005	0.003		05.00	SMALL
X	1	100.0	020.2	0.005	0.003	02.28	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.2E-7	2.25	.23		24H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
A	X 00020.20	24H-70F-25.9% OXYGEN 24H-150F-

TOXICITY

65967 ADHESIVE BOSTIK 1252
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65968 ADHESIVE BOSTIK 1315
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65969 ADHESIVE BOSTIK 1372
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65970 ADHESIVE BOSTIK 1376
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65971 ADHESIVE BOSTIK 1398
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005165 0 ■

Information Handling Services, 2000

65972 ADHESIVE BOSTIK 1515
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65973 ADHESIVE BOSTIK 1530
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65974 ADHESIVE BOSTIK 1600
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

84002 ADHESIVE BOSTIK 2000
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65975 ADHESIVE BOSTIK 2009
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65976 ADHESIVE BOSTIK 2315
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65977 ADHESIVE BOSTIK 2363
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65978 ADHESIVE BOSTIK 2378
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65979 ADHESIVE BOSTIK 2425
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

84003 ADHESIVE BOSTIK 3000
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

83999 ADHESIVE BOSTIK 320
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

84004 ADHESIVE BOSTIK 4000
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65980 ADHESIVE BOSTIK 4025
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65981 ADHESIVE BOSTIK 4101
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005166 2

Information Handling Services, 2000

65982 ADHESIVE BOSTIK 4165
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65983 ADHESIVE BOSTIK 4252
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65984 ADHESIVE BOSTIK 4342
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

84000 ADHESIVE BOSTIK 620
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65985 ADHESIVE BOSTIK 6323
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65986 ADHESIVE BOSTIK 6330
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65987 ADHESIVE BOSTIK 6368
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65988 ADHESIVE BOSTIK 7008
MANF: BOSTIK FINCH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.75	.21	.00	1H-148F- 5H-275F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61047 ADHESIVE BOSTIK 7376 GID: ABCQXX
MANF: BOSTIK FINCH

SPEC: SVHS 10091

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.012	0.003	00.00	00.00	NONE
A	1	100.0	020.2	0.012	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.8E-6	3.24	.18	.43	

ODOR

RT	RT WEIGHT	CURE
A	K 00002.72	

TOXICITY

65989 ADHESIVE BOSTIK 7431
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65990 ADHESIVE BOSTIK 7432
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65991 ADHESIVE BOSTIK 7433
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

65992 ADHESIVE BOSTIK 7434
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65993 ADHESIVE BOSTIK 7435
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65994 ADHESIVE BOSTIK 8230
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65995 ADHESIVE BOSTIK 8323
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65996 ADHESIVE BOSTIK 8330
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65997 ADHESIVE BOSTIK 8363
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65998 ADHESIVE BOSTIK 8375
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

65999 ADHESIVE BOSTIK 8376
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

66000 ADHESIVE BOSTIK 8377
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

66001 ADHESIVE BOSTIK 8378
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

66002 ADHESIVE BOSTIK 8379
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

84001 ADHESIVE BOSTIK 920
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

84005 ADHESIVE BOSTIK 9732
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

67678 ADHESIVE BR104 EPOXY
MANF: EPOXYLITE CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005168 6 ■

Information Handling Services, 2000

67684 ADHESIVE BR22
MANF: EPOXYLITE CORP
....NO TEST DATA AVAILABLE....

67681 ADHESIVE BR610
MANF: WILLIAM T. BEAN MICRO ENGINEER

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.62	.02	.00	1H-350F-	No test data		

65681 ADHESIVE BR624
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

65682 ADHESIVE BR626
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

65683 ADHESIVE BR662
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

80615 ADHESIVE BR92A
MANF: AMERICAN CYANAMID

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.80	.02	.00	1.5H-212F-	No test data		

80616 ADHESIVE BR95
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

66894 ADHESIVE BRUTEM 14
MANF: I W INDUSTRIES INC
....NO TEST DATA AVAILABLE....

66892 ADHESIVE BRUTEM 17
MANF: I W INDUSTRIES INC
....NO TEST DATA AVAILABLE....

66891 ADHESIVE BRUTEM 33
MANF: I W INDUSTRIES INC
....NO TEST DATA AVAILABLE....

66890 ADHESIVE BRUTEM 506
MANF: I W INDUSTRIES INC
....NO TEST DATA AVAILABLE....

66893 ADHESIVE BRUTEM 78
MANF: I W INDUSTRIES INC
....NO TEST DATA AVAILABLE....

82106 ADHESIVE BRUTEM 91
MANF: I W INDUSTRIES INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005169 8

82107 ADHESIVE BRUTEM 92
MANF: I W INDUSTRIES INC
....NO TEST DATA AVAILABLE....

66898 ADHESIVE BRUTUM 19
MANF: I W INDUSTRIES INC
....NO TEST DATA AVAILABLE....

66896 ADHESIVE BRUTUM 19HF
MANF: I W INDUSTRIES INC
....NO TEST DATA AVAILABLE....

66897 ADHESIVE BRUTUM 19MP
MANF: I W INDUSTRIES INC
....NO TEST DATA AVAILABLE....

60368 ADHESIVE BSL 119 PRIMER GID: AUXXXX
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

64909 ADHESIVE BSL 208/5 FOAM
MANF: CIBA-GEIGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.64	.13	.77	1H-338F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60359 ADHESIVE BSL 312 GID: ABXXXX
MANF: CIBA-GEIGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.81	.23	.00	1H-320F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60367 ADHESIVE BSL 319 GID: ABXXXX
MANF: CIBA-GEIGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.19	.03	.00	3H-347F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

67194 ADHESIVE C111
MANF: STABOND CORP
....NO TEST DATA AVAILABLE....

05584 ADHESIVE C15-015 A/B EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	023.8	014.5	0.034	0.003		04.10		SMALL
C	2	025.9	014.3	0.017	0.003	00.00	00.00		NONE
C	1	025.9	014.3	0.017	0.003	00.18	12.00	T	NONE
X	1	030.0	008.0	0.030	0.010	00.41	12.00	T	MOD
X	1	040.0	008.0	0.030	0.010	00.51	12.00	T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.99	.05		16H-185F- 4H-225F-

ODOR

RT	RT WEIGHT	CURE
A	X 00022.65	16H-185F- 4H-225F-

TOXICITY

MSFC-HDBK-527 REV F 9999942 0005170 4

Information Handling Services, 2000

05228 ADHESIVE C7-4248 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.66	.23	.00	2H-257F- 16H-284F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05817 ADHESIVE C9-4198/H2-3561 GID: ABBGXX
MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.028	0.003		00.30	NONE
C	1	023.8	014.5	0.028	0.003	00.10	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.2E-7	.43	.03		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00170.94	168H-70F-

61505 ADHESIVE C9-4210 AND 4215/H3469 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER
P0109/P0209/P0203

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.074			00.30	NONE
C	1	023.8	014.5	0.074		00.20	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.1E-7	.69	.41		2H-203F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00020.11	2H-203F-

05743 ADHESIVE C9-42101/H3561 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.031		00.51	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61993 ADHESIVE C9-4215/H3561 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.016	0.003	00.26	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.60	.00	.00	2.5H-223F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00020.02	24H-70F-

67677 ADHESIVE CA2005L
MANF: WILLIAM T. BEAN MICRO ENGINEER
....NO TEST DATA AVAILABLE....

69618 ADHESIVE CA3
MANF: 3M CO
....NO TEST DATA AVAILABLE....

69619 ADHESIVE CA4
MANF: 3M CO
....NO TEST DATA AVAILABLE....

69620 ADHESIVE CA40
MANF: 3M CO

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005171 6

69621 ADHESIVE CA40H
MANF: 3M CO
....NO TEST DATA AVAILABLE....

69622 ADHESIVE CA5
MANF: 3M CO
....NO TEST DATA AVAILABLE....

69623 ADHESIVE CA7
MANF: 3M CO
....NO TEST DATA AVAILABLE....

69624 ADHESIVE CA8
MANF: 3M CO
....NO TEST DATA AVAILABLE....

69625 ADHESIVE CA9
MANF: 3M CO
....NO TEST DATA AVAILABLE....

84423 ADHESIVE CADCO BA400
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

84424 ADHESIVE CADCO BA500
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

84425 ADHESIVE CADCO PS18
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

84426 ADHESIVE CADCO PS30
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

20465 ADHESIVE CANADA BALSAM GID: ABXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	20.36	4.15	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

67254 ADHESIVE CASE SEALING ADHESIVE EC4365
MANF: 3M CO
....NO TEST DATA AVAILABLE....

66008 ADHESIVE CASTALL 110 A/B
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

20770 ADHESIVE CASTALL 1520/E34 EPOXY GID: ABBGXX
MANF: CASTALL INC SPEC: HS 6074T/B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.100		00.00	00.00	NONE
C	1	025.9	014.3	0.100		00.08	12.00	T SMALL
C	1	025.9	014.3	0.106		00.06	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

	PRESS	TML%	VCM%	RML%	CURE
	1.1E-6	.25	.01	.10	16H-150F-

ODOR

RT	RT WEIGHT	CURE
A	B 00020.24	16H-149F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005172 8

66004 ADHESIVE CASTALL 1520/RT70

MANF: CASTALL INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.95	.05	.00	.75H-148F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66005 ADHESIVE CASTALL 1520/RT 1

MANF: CASTALL INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.006	0.003		03.50	NONE
X	1	100.0	020.2	0.004	0.003	2.00	12.00	T NONE
X	2	100.0	020.2	0.006	0.003	0.200	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.0E-6	.33	.05	.11	

ODOR

RT	RT WEIGHT	CURE
A	K 21.515	

TOXICITY

66006 ADHESIVE CASTALL 1520/RT 7

MANF: CASTALL INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.25	.07	.00	.75H-148F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66009 ADHESIVE CASTALL 2009

MANF: CASTALL INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.72	.05	.91	168H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66010 ADHESIVE CASTALL 310 A/B

MANF: CASTALL INC

....NO TEST DATA AVAILABLE....

66011 ADHESIVE CASTALL 341

MANF: CASTALL INC

....NO TEST DATA AVAILABLE....

20295 ADHESIVE CASTALL 343 EPOXY GID: ABBGXX

MANF: CASTALL INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.004	0.003		05.30	NONE
A	1	030.0	009.0	0.004	0.125	00.00	00.00	NONE
X	1	033.0	014.3	0.009	0.003	00.55	12.00	T NONE
I	1	100.0	016.5	0.004	0.003	00.89	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.85	.05	.00	3H-176F-

ODOR

RT	RT WEIGHT	CURE
A	B 00010.95	2H-149F- 4H-275F-

TOXICITY

66012 ADHESIVE CASTALL 4874

MANF: CASTALL INC

....NO TEST DATA AVAILABLE....

66021 ADHESIVE CASTALL 4875

MANF: CASTALL INC

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005173 T

66013 ADHESIVE CASTALL 6612
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

69604 ADHESIVE CASTALL A
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66007 ADHESIVE CASTALL A343
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66014 ADHESIVE CASTALL D
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66015 ADHESIVE CASTALL E
MANF: CASTALL INC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.51	.00	.00	12H-149F-	No test data		

66022 ADHESIVE CASTALL E100
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66023 ADHESIVE CASTALL E105
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66024 ADHESIVE CASTALL E106
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66040 ADHESIVE CASTALL E1530/E34
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66025 ADHESIVE CASTALL E300
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66026 ADHESIVE CASTALL E301
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66027 ADHESIVE CASTALL E301AD
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66028 ADHESIVE CASTALL E301KT
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66029 ADHESIVE CASTALL E341
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005174 1

66041 ADHESIVE CASTALL E341FR
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66030 ADHESIVE CASTALL E401
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66031 ADHESIVE CASTALL E403
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66032 ADHESIVE CASTALL E409
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66042 ADHESIVE CASTALL E435/E34
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66043 ADHESIVE CASTALL E463/E34
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66044 ADHESIVE CASTALL E464/E34
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66045 ADHESIVE CASTALL E466/E34
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66033 ADHESIVE CASTALL E480 A
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66034 ADHESIVE CASTALL E482 A
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66035 ADHESIVE CASTALL E483 A
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66046 ADHESIVE CASTALL E492/E34 FR
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66016 ADHESIVE CASTALL F
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66017 ADHESIVE CASTALL G
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005175 3

Information Handling Services, 2000

66018 ADHESIVE CASTALL H
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66038 ADHESIVE CASTALL J/E34
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66019 ADHESIVE CASTALL J/RT 1
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66020 ADHESIVE CASTALL J/RT 7A
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66047 ADHESIVE CASTALL K/E34
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66036 ADHESIVE CASTALL K/RT 7A HI-IMPACT EPOXY
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66039 ADHESIVE CASTALL QUICK CURE
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84929 ADHESIVE CASTALL S1277
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84931 ADHESIVE CASTALL U2001
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84935 ADHESIVE CASTALL U2002
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84525 ADHESIVE CASTALL U2003
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84528 ADHESIVE CASTALL U2004
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66051 ADHESIVE CASTALL U2006
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84529 ADHESIVE CASTALL U2007
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005176 5 ■

Information Handling Services, 2000

66048 ADHESIVE CASTALL U2008
MANF: CASTALL INC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	3.26	.01	2.16	24H-46F- 168H-46F-	No test data		

84579 ADHESIVE CASTALL U2009
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84581 ADHESIVE CASTALL U2010
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84582 ADHESIVE CASTALL U2012
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84583 ADHESIVE CASTALL U2015
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66052 ADHESIVE CASTALL U2017
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84585 ADHESIVE CASTALL U2018
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84587 ADHESIVE CASTALL U2019
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84589 ADHESIVE CASTALL U2020
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84592 ADHESIVE CASTALL U2020FR
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84595 ADHESIVE CASTALL U2024
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84597 ADHESIVE CASTALL U2028
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66050 ADHESIVE CASTALL U2032
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84601 ADHESIVE CASTALL U2036
MANF: CASTALL INC

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005177 7

84602 ADHESIVE CASTALL U2040
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

66049 ADHESIVE CASTALL U2044
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84603 ADHESIVE CASTALL U2048
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

84605 ADHESIVE CASTALL U2052
MANF: CASTALL INC
....NO TEST DATA AVAILABLE....

61379 ADHESIVE CAVALON 3300S/3101S GID: ABAKXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.004	0.003		02.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.8E-6	5.33	.44		24H-70F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
B	00090.37	24H-70F-

66725 ADHESIVE CB10
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

60108 ADHESIVE CCX536/3561 GID: ABXXXX
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

60385 ADHESIVE CEMABOND 571 GID: ABXXXX
....NO TEST DATA AVAILABLE....

20060 ADHESIVE CEMENT PS18 ACRYLIC GID: ABAKXX
MANF: CHEMICAL DEVELOPMENT CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.74	.00	.00	72H-70F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

65801 ADHESIVE CERAMABOND 552
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

65802 ADHESIVE CERAMABOND 569
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

65810 ADHESIVE CERAMABOND 618
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

06178 ADHESIVE CERAMIC 503 INORGANIC GID: ABXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
	1.0E-6	.07	.00	.00	1H-77F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005178 9

06178 ADHESIVE CERAMIC 503 INORGANIC (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					1H-268F-
					16H-538F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE

20087 ADHESIVE CERAMIC APCO R310 EPOXY GID: ABHOBG
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

60088 ADHESIVE CERAMIC MITHRA 200 GID: ABXXXX
MANF: MITHRA
....NO TEST DATA AVAILABLE....

60078 ADHESIVE CERAMIC TYCEMENT UF3206 GID: ABHOXX
MANF: THIOKOL SPEC: STW5-2655
....NO TEST DATA AVAILABLE....

60153 ADHESIVE CERAMIC TYCEMENT UF3242 GID: ABHOXX
MANF: THIOKOL
....NO TEST DATA AVAILABLE....

60688 ADHESIVE CERAMIC ULTRATEMP 516 GID: AKHOFK
MANF: AREMCO PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.090		00.00	00.00	NONE
A	1	043.2	008.0	0.027		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00036.26	

66055 ADHESIVE CERMALLOY 5100
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66056 ADHESIVE CERMALLOY 5200
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66057 ADHESIVE CERMALLOY 5200F
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66058 ADHESIVE CERMALLOY 5300
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66059 ADHESIVE CERMALLOY 5500
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66060 ADHESIVE CERMALLOY PC200S
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005179 0

66061 ADHESIVE CERMALLOY PC300S
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

62344 ADHESIVE CERMALLOY T2000 EPOXY GID: ABBGXX
MANF: CERMALLOY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.52	.00	.43	1H-300F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

62343 ADHESIVE CERMALLOY T2100 EPOXY GID: ABBGXX
MANF: CERMALLOY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.20	.00	.17	1H-248F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

66062 ADHESIVE CERMALLOY T2100T
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66063 ADHESIVE CERMALLOY T2110
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66064 ADHESIVE CERMALLOY T2110T
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66065 ADHESIVE CERMALLOY T2200
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66066 ADHESIVE CERMALLOY T2210
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66067 ADHESIVE CERMALLOY T2300
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66068 ADHESIVE CERMALLOY T2310
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66069 ADHESIVE CERMALLOY T2800
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66070 ADHESIVE CERMALLOY T2810
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66071 ADHESIVE CERMALLOY T2811
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005180 7

Information Handling Services, 2000

66072 ADHESIVE CERMALLOY T2900
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66073 ADHESIVE CERMALLOY UVC500
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

66074 ADHESIVE CERMALLOY UVI100
MANF: CERMALLOY
....NO TEST DATA AVAILABLE....

63295 ADHESIVE CHEMGRIP GID: ABXXXX
MANF: CHEMPLAST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00006.54	

67106 ADHESIVE CHEMGRIP 34
MANF: NORTON
....NO TEST DATA AVAILABLE....

60173 ADHESIVE CHEMLOK GID: ABXXXX
MANF: LORD CORP
SPEC: STW5-2870
....NO TEST DATA AVAILABLE....

69615 ADHESIVE CHEMLOK 2
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

02231 ADHESIVE CHEMLOK 205 PRIMER WITH CHEMLOK 220 TOPCOAT GID: ABDBXX
MANF: LORD CORP
SPEC: LCD0607/LCC0618 MB0120-028

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.001	0.003		01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.35	.00	.00	.5H-70F- .17H-320F-

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE
X	00004.96	

60120 ADHESIVE CHEMLOK 233 GID: ABXXXX
MANF: LORD CORP
SPEC: STW5-2712
....NO TEST DATA AVAILABLE....

61487 ADHESIVE CHEMLOK 234 GID: ABXXXX
MANF: LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	15.55	.11	.00	.5H-77F- .5H-300F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

62720 ADHESIVE CHEMLOK 234B GID: ABXXXX
MANF: LORD CORP
SPEC: STW 5-2721

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005181 9

66944 ADHESIVE CHEMLOK 235
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66945 ADHESIVE CHEMLOK 236A
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66946 ADHESIVE CHEMLOK 238
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66947 ADHESIVE CHEMLOK 246
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

06343 ADHESIVE CHEMLOK 250 GID: ABDEXX
MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		01.60	NONE
C	1	030.0	009.0	0.001	0.003	02.31	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	100	72	250	0.001	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	23.25	1.11	.12	.67H-46F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

66948 ADHESIVE CHEMLOK 252
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66949 ADHESIVE CHEMLOK 253
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

20580 ADHESIVE CHEMLOK 304 GID: ABBGXX
MANF: LORD CORP SPEC: ST32A971-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.006	0.003	00.71	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-6	1.88	.08		24H-70F-
					24H-150F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00020.99	24H-70F-
		24H-150F-

66950 ADHESIVE CHEMLOK 402
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

05439 ADHESIVE CHEMLOK 607 GID: ABXXXX
MANF: LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	12.62	1.02	.00	24H-300F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

60152 ADHESIVE CHEMLOK 608 GID: ABBGXX
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005182 0

66951 ADHESIVE CHEMLOK 810
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

62082 ADHESIVE CHEMLOK AP131 GID: ABXXXX
MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		01.20	NONE
A	1	033.0	014.3	0.001	0.003		01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.8E-6	3.46	.00		24H-70F- 24H-150F-

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE
B	00021.73	24H-70F- 24H-150F-

66952 ADHESIVE CHEMLOK BN
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66973 ADHESIVE CHEMLOK FR
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66969 ADHESIVE CHEMLOK G
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66970 ADHESIVE CHEMLOK GM
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66974 ADHESIVE CHEMLOK LR
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66971 ADHESIVE CHEMLOK M
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66972 ADHESIVE CHEMLOK P
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66975 ADHESIVE CHEMLOK R
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

20296 ADHESIVE CHEMOTEC 805/805B GID: ABBGXX
....NO TEST DATA AVAILABLE....

81120 ADHESIVE CHERABOND 18
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

61086 ADHESIVE CHOBOND 1029 GID: ABCKXX
MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
[illegible]	[illegible]	38	16	00	1H-151F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005183 2

61087 ADHESIVE CHOBOND 1030 GID: ABCKXX
MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.31	.12	.00	168H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06617 ADHESIVE CHOBOND 1030/1086 SILICONE GID: ABCKXX
MANF: CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.013	0.003		00.60	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	2.2E-6	.08	.04	.01	.33H-70F-ONE BRUSH COAT OF PRIMER NO. 1986 WAS APPLIED. 1H-70F-NO. 1030 ADHESIVE WAS APPLIED WITH A SPATULA OVER THE PREVIOUSLY CURED PRIMER. 4H-300F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66075 ADHESIVE CHOBOND 1035
MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.08	.65	.00	168H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66076 ADHESIVE CHOBOND 1038
MANF: CHOMERICS
....NO TEST DATA AVAILABLE....

60351 ADHESIVE CHOBOND 320 GID: ABXXXX
MANF: CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.3	0.015			01.20	NONE
A	1	025.9	014.3	0.001	0.003		01.50	NONE
A	1	025.9	014.3	0.015			02.42	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	9.94	3.62	.24	

ODOR

RT	RT WEIGHT	CURE
X	00003.75	

TOXICITY

61560 ADHESIVE CHOBOND 350A/B WITH 1086PRI GID: ABCKXX
MANF: CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010	0.003		01.60	NONE
A	1	030.0	009.0	0.010	0.003		01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.5E-6	.33	.04	.03	4H-150F-

ODOR

RT	RT WEIGHT	CURE
A	B 00020.58	4H-150F-

TOXICITY

66077 ADHESIVE CHOBOND 360-18
MANF: CHOMERICS
....NO TEST DATA AVAILABLE....

66078 ADHESIVE CHOBOND 360-20
MANF: CHOMERICS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005184 4

66079 ADHESIVE CHOBOND 360-208
MANF: CHOMERICS
....NO TEST DATA AVAILABLE....

66080 ADHESIVE CHOBOND 4660
MANF: CHOMERICS
....NO TEST DATA AVAILABLE....

66081 ADHESIVE CHOBOND 4669
MANF: CHOMERICS
....NO TEST DATA AVAILABLE....

69903 ADHESIVE CHOBOND 584 CONDUCTIVE EPOXY
MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	01.09	00.02	00.99	2H-149F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66082 ADHESIVE CHOBOND 584-208
MANF: CHOMERICS
....NO TEST DATA AVAILABLE....

05552 ADHESIVE CHOBOND 584-29 CON/EPOXY GID: ABBGXX
MANF: CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.005	0.003	00.00	00.00	NONE
B	1	025.9	014.3	0.005	0.003	00.30	08.90	SMALL
B	1	030.0	010.0	0.005	0.003	00.30	07.00	SMALL
X	2	030.0	010.0	0.010	0.003	00.00	00.00	NONE
X	1	030.0	010.0	0.010	0.003	00.10	08.20	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.16	.04	.00	.75H-212F-

ODOR

RT	RT WEIGHT	CURE
A	X 00021.53	24H-70F-

TOXICITY

66083 ADHESIVE CHOBOND 592
MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.26	.01	.00	8H-212F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60215 ADHESIVE CHOMERICS 360 EPOXY GID: ABXXXX
MANF: CHOMERICS
....NO TEST DATA AVAILABLE....

60845 ADHESIVE CMC19-2 GID: ABXXXX
MANF: OAK INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.002	0.003	00.00	00.00	NONE
B	1	020.9	014.7	0.002	0.003		07.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	5.52	2.93		2H-335F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60839 ADHESIVE CMC634-2 GID: ABXXXX
MANF: OAK INDUSTRIES

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005185 6

60839 ADHESIVE CMC634-2 (cont)

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	3.6E-7	3.15	.04			No test data		

67201 ADHESIVE CON/RTV-I
MANF: TECKNIT
....NO TEST DATA AVAILABLE....

67202 ADHESIVE CON/RTV-II
MANF: TECKNIT
....NO TEST DATA AVAILABLE....

67203 ADHESIVE CON/RTV-NI
MANF: TECKNIT
....NO TEST DATA AVAILABLE....

67199 ADHESIVE CON/RTV-SC
MANF: TECKNIT
....NO TEST DATA AVAILABLE....

66145 ADHESIVE CONAP AD1146
MANF: CONAP
....NO TEST DATA AVAILABLE....

66146 ADHESIVE CONAP AD1146-1
MANF: CONAP
....NO TEST DATA AVAILABLE....

66147 ADHESIVE CONAP AD1146C
MANF: CONAP
....NO TEST DATA AVAILABLE....

66148 ADHESIVE CONAP AD1146C1
MANF: CONAP
....NO TEST DATA AVAILABLE....

66149 ADHESIVE CONAP AD1147
MANF: CONAP
....NO TEST DATA AVAILABLE....

66150 ADHESIVE CONAP AD1147-1
MANF: CONAP
....NO TEST DATA AVAILABLE....

66151 ADHESIVE CONAP AD1147C
MANF: CONAP
....NO TEST DATA AVAILABLE....

66152 ADHESIVE CONAP AD1147C1
MANF: CONAP
....NO TEST DATA AVAILABLE....

66153 ADHESIVE CONAPOXY AD1000
MANF: CONAP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005186 8 ■

Information Handling Services, 2000

67637 ADHESIVE CONAPOXY AD1040B/CONACURE EA073A
MANF: CONAP
....NO TEST DATA AVAILABLE....

66154 ADHESIVE CONAPOXY AD11
MANF: CONAP
....NO TEST DATA AVAILABLE....

66155 ADHESIVE CONAPOXY AD12
MANF: CONAP
....NO TEST DATA AVAILABLE....

66156 ADHESIVE CONAPOXY AD13
MANF: CONAP
....NO TEST DATA AVAILABLE....

66157 ADHESIVE CONAPOXY AD14
MANF: CONAP
....NO TEST DATA AVAILABLE....

66158 ADHESIVE CONAPOXY AD17
MANF: CONAP
....NO TEST DATA AVAILABLE....

61578 ADHESIVE CONAPOXY FR1241/EA4 GID: ABBGXX
MANF: CONAP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.008	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.008	0.003	00.80	12.00	T SMALL
C	2	030.0	010.0	0.007	0.003	00.00	00.00	NONE
C	1	030.0	010.0	0.007	0.003	00.60	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.9E-6	1.83	.03	.25	24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.46	24H-70F-

66159 ADHESIVE CONASTIC 830 OIL/GRIP
MANF: CONAP
....NO TEST DATA AVAILABLE....

66160 ADHESIVE CONASTIC AD20
MANF: CONAP
....NO TEST DATA AVAILABLE....

66161 ADHESIVE CONASTIC G1 SERIES
MANF: CONAP
....NO TEST DATA AVAILABLE....

66162 ADHESIVE CONASTIC ST115 GID: ABCQXX
MANF: CONAP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	020.2	0.060		01.00	12.00	T LARGE
X	1	100.0	020.2	0.060		02.00	12.00	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.0E-6	.85	.03	.14	144H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	21.326	144H-70F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005187 T

66122 ADHESIVE CONBOND
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

61808 ADHESIVE CONBOND 1560 N/F GID: ABXXXX
MANF: COLUMBIA CEMENT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.19	.08	.00	4H-160F-0psiaVACUUM

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00001.20	72H-70F-

66110 ADHESIVE CONBOND 1736 N/F SPRAY
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

61807 ADHESIVE CONBOND 2103 N/F GID: ABXXXX
MANF: COLUMBIA CEMENT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.70	NONE
A	1	023.8	014.5	0.004	0.003		01.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.4E-6	2.81	.11		2H-160F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00001.42	72H-70F-

66111 ADHESIVE CONBOND 2153
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66125 ADHESIVE CONBOND 2214 N/F SUPER SPRAY
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66112 ADHESIVE CONBOND 2448
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66113 ADHESIVE CONBOND 2466
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66124 ADHESIVE CONBOND 2620
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66118 ADHESIVE CONBOND 272SP
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66126 ADHESIVE CONBOND 2849 N/F SPRAY
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66121 ADHESIVE CONBOND 2960
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005188 1

66119 ADHESIVE CONBOND 2979
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66120 ADHESIVE CONBOND 3004
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66114 ADHESIVE CONBOND 310 WATER BASED CONTACT
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66117 ADHESIVE CONBOND 330
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66115 ADHESIVE CONBOND 360
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66116 ADHESIVE CONBOND 773
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66123 ADHESIVE CONBOND 773-40
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66127 ADHESIVE CONBOND 985
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

60794 ADHESIVE CONBOND CONTACT CEMENT GID: ABCQXX
MANF: COLUMBIA CEMENT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.50	NONE
A	1	023.8	014.5	0.003	0.003		01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.8E-7	2.20	.05		24H-160F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00001.10	24H-70F-

65631 ADHESIVE CONCRESIVE
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65634 ADHESIVE CONCRESIVE 1064
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65635 ADHESIVE CONCRESIVE 1170
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65636 ADHESIVE CONCRESIVE 1305
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

65637 ADHESIVE CONCRESIVE 1310
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65638 ADHESIVE CONCRESIVE 1411
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65639 ADHESIVE CONCRESIVE 1419
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65640 ADHESIVE CONCRESIVE 1422
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65641 ADHESIVE CONCRESIVE 1438
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65642 ADHESIVE CONCRESIVE 1440
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65643 ADHESIVE CONCRESIVE 1441
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65644 ADHESIVE CONCRESIVE 3007
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65645 ADHESIVE CONCRESIVE 3008
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65646 ADHESIVE CONCRESIVE 3009
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65648 ADHESIVE CONCRESIVE 3013
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65649 ADHESIVE CONCRESIVE 3014
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65650 ADHESIVE CONCRESIVE 3034
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65651 ADHESIVE CONCRESIVE 3042 PENSEAL 50
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005190 T ■

Information Handling Services, 2000

65652 ADHESIVE CONCRESIVE AEX1470
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65655 ADHESIVE CONCRESIVE AEX1482X
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65656 ADHESIVE CONCRESIVE AEX1533G
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65653 ADHESIVE CONCRESIVE AEX1539G
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65657 ADHESIVE CONCRESIVE GLOSSFIX 1409
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65894 ADHESIVE CONDUCTING 20/20
MANF: BACON
....NO TEST DATA AVAILABLE....

65347 ADHESIVE CONDUCTIVE VERSATAC PAD GID: ABXXXX
MANF: CONMED

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.070	0.003		00.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00024.99	

66364 ADHESIVE CONTACT 1001
MANF: DIMITER EMULSION & CHEMICAL
....NO TEST DATA AVAILABLE....

69602 ADHESIVE CPVC CEMENT AA1106HB
MANF: ARROW ADHESIVES CO
....NO TEST DATA AVAILABLE....

81695 ADHESIVE CR3125
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

62398 ADHESIVE CRACK 'N PEEL GID: ABXXXX
MANF: AVERY INTERNATIONAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.9E-6	4.92	.69	2.40	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00011.08	

65943 ADHESIVE CRAFTER'S EPOXY
MANF: BEECHAM
....NO TEST DATA AVAILABLE....

65942 ADHESIVE CRAFTER'S FAST EPOXY
MANF: BEECHAM
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005191 1

66171 ADHESIVE CREST 1013 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66172 ADHESIVE CREST 141 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66173 ADHESIVE CREST 170
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66174 ADHESIVE CREST 173 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66175 ADHESIVE CREST 2027 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66176 ADHESIVE CREST 2053 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66180 ADHESIVE CREST 2079 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66179 ADHESIVE CREST 2092 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66195 ADHESIVE CREST 2154 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66197 ADHESIVE CREST 2800 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66181 ADHESIVE CREST 3119 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66182 ADHESIVE CREST 3120 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66183 ADHESIVE CREST 3133 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66184 ADHESIVE CREST 3135 A/B
MANF: CREST PRODUCTS

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.12	.04		

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

MSFC-HDBK-527 REV F 9999942 0005192 3

Information Handling Services, 2000

66185 ADHESIVE CREST 3144 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66186 ADHESIVE CREST 3147 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66177 ADHESIVE CREST 3170 A/B
MANF: CREST PRODUCTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.25	.09	.00	16H-70F- 2H-122F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66188 ADHESIVE CREST 3181
MANF: CREST PRODUCTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.55	.13	.26	1H-212F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66189 ADHESIVE CREST 391 A/B
MANF: CREST PRODUCTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	26.86	7.58	.00	120H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66196 ADHESIVE CREST 4096 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66178 ADHESIVE CREST 627
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66190 ADHESIVE CREST 642 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66191 ADHESIVE CREST 723 A/B GID: ABBGXX
MANF: CREST PRODUCTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	6.0E-6	00.72	00.05	00.20	1H-150F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65300 ADHESIVE CREST 7344 A/B GID: ABBGXX
MANF: CREST PRODUCTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.78	.66	.00	504H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60141 ADHESIVE CREST 7450 POLYURETHANE GID: ABCQXX
MANF: CREST PRODUCTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.71	.30	.00	168H-70F- 16H-176F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005193 5

66192 ADHESIVE CREST 760 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66193 ADHESIVE CREST 800 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

66194 ADHESIVE CREST 805 A/B
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

84400 ADHESIVE CREST 837
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

84398 ADHESIVE CRYOSEAL 2132
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

84399 ADHESIVE CRYOSEAL 605
MANF: CREST PRODUCTS
....NO TEST DATA AVAILABLE....

65803 ADHESIVE CRYSTALBOND 509 TEMPORARY WASH-AWAY
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

65804 ADHESIVE CRYSTALBOND 555 TEMPORARY WASH-AWAY
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

65805 ADHESIVE CRYSTALBOND 590 TEMPORARY WASH-AWAY
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

66726 ADHESIVE CT20
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66417 ADHESIVE CUPRINOL OUTDOOR CAULK
MANF: E B INDUSTRIES
....NO TEST DATA AVAILABLE....

67532 ADHESIVE CV1142
MANF: MCGHAN NUSIL
....NO TEST DATA AVAILABLE....

67533 ADHESIVE CV1143
MANF: MCGHAN NUSIL

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.34	.05	.28	168H-46F-	No test data		

67534 ADHESIVE CV12570
MANF: MCGHAN NUSIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005194 7

Information Handling Services, 2000

67535 ADHESIVE CV2564
MANF: MCGHAN NUSIL
....NO TEST DATA AVAILABLE....

67536 ADHESIVE CV2568
MANF: MCGHAN NUSIL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.38	.07	.00	168H-70F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

61178 ADHESIVE CVV GID: ABXXXX
MANF: HERCULITE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.006	0.003	00.18	06.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00019.58	8H-70F-

66101 ADHESIVE CY8043-1
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

63294 ADHESIVE CYANOACRYLATE GID: ABXXXX
MANF: LOCTITE CORP SPEC: NSN 8040-00-142-9193

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00001.60	

66587 ADHESIVE CYCLEWELD
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66554 ADHESIVE CYCLEWELD 5420A/640A
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

05963 ADHESIVE CYCLEWELD 55-9 GID: ABBGXX
MANF: FIBER-RESIN CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005	0.003		05.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.32	.48	.00	.05H-160F- .5H-270F-

ODOR

RT
X

TOXICITY

RT	RT WEIGHT	CURE
X	00006.78	.33H-325F-

66555 ADHESIVE CYCLEWELD C14
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66586 ADHESIVE CYCLEWELD K114 A/B
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

64195 ADHESIVE DAC1 GID: AACKXX
MANF: DR. DANIEL WOODARD

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005195 9

64195 ADHESIVE DAC1 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.007	0.003		02.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00022.46	

TOXICITY

64107 ADHESIVE DAC2 SILICONE GID: BNXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.008	0.003	00.14	03.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00022.25	

TOXICITY

60172 ADHESIVE DAP GID: ABXXXX

MANF: DAP INC SPEC: MIL-D-13796

....NO TEST DATA AVAILABLE....

65930 ADHESIVE DAP 2000 CONSTRUCTION

MANF: BEECHAM

....NO TEST DATA AVAILABLE....

65931 ADHESIVE DAP 4000 SUB FLOOR AND PLYWOOD

MANF: BEECHAM

....NO TEST DATA AVAILABLE....

69603 ADHESIVE DAP FUNTAK

MANF: BEECHAM
HOME IMPROVEMENT PROD

....NO TEST DATA AVAILABLE....

65935 ADHESIVE DAP GLUE STICK

MANF: BEECHAM

....NO TEST DATA AVAILABLE....

65938 ADHESIVE DAP PERMABOND SUPER GLUE

MANF: BEECHAM

....NO TEST DATA AVAILABLE....

65937 ADHESIVE DAP PERMABOND SUPER GLUE FOR WOOD AND LEATHER

MANF: BEECHAM

....NO TEST DATA AVAILABLE....

05155 ADHESIVE DAPCOTAC 3001 GID: ABXXXX

MANF: AIRCRAFT PRODUCTS SPEC: MB0120-025

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		02.30	NONE
A	1	030.0	010.4	0.001	0.003		02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.96	.41	.40	17H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	X	00010.30	17H-70F-

TOXICITY

05512 ADHESIVE DAPCOTAC 3008 EPOXY GID: ABBGXX

MANF: D AIRCRAFT PRODUCTS

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005196 0 ■

65936 ADHESIVE DAPTAK REUSABLE
MANF: BEECHAM
....NO TEST DATA AVAILABLE....

84968 ADHESIVE DC 92-009
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

00895 ADHESIVE DC281 SILICONE WITH CATALYST GID: ABCKXX
MANF: DOW CORNING SPEC: AH058626 AH058905

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.003		02.70	NONE
A	1	030.0	010.0	0.010	0.003		01.80	NONE
A	1	033.0	014.3	0.003	0.003		05.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.43	1.38	.00	24H-138F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00011.32	24H-70F- .08H-302F-

60204 ADHESIVE DC282 GID: ABXXXX
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.45	.09	.00	16H-194F- 8H-150F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

60355 ADHESIVE DC6-1004 GID: ABXXXX
MANF: DOW CORNING SPEC: LAC40-4452
....NO TEST DATA AVAILABLE....

84962 ADHESIVE DC6-1125
MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010	0.003		05.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.22	.02		168H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

84971 ADHESIVE DC92-010 RUBBER SILICONE
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

00898 ADHESIVE DC92-018 SILICONE GID: ABCKXX
MANF: DOW CORNING SPEC: MB0120-054

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.00	.83	.00	120H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00024.52	24H-150F-

84974 ADHESIVE DC93-006
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

84977 ADHESIVE DC93-118
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005197 2

05199 ADHESIVE DC94-002 FLUOROSILICONE RUBBER GID: DPDGXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.073	0.003		01.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		70	0.066	02	03
X	MECH	1500	72	70	0.099	2	44
Z	MECH	1500	72	70	0.099	2	44

THERMAL VACUUM STABILITY

RT	PRESS-	TML%	VCM%	RML%	CURE
C	3.8E-7	2.62	.06		168H-70F- 24H-150F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00200.83	168H-70F- 24H-150F-

84980 ADHESIVE DC94-011

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

84982 ADHESIVE DC94-031

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

05700 ADHESIVE DC96-069 SILICONE GID: ABCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.009	0.003		02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.5E-5	.57	.16		4H-158F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00042.37	4H-158F-

67639 ADHESIVE DC96-081 RTV

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

84984 ADHESIVE DC96-082 RUBBER SILICONE

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

67640 ADHESIVE DC96-083

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

66462 ADHESIVE DELTABOND 152 WITH A4

MANF: WAKEFIELD

....NO TEST DATA AVAILABLE....

05612 ADHESIVE DELTABOND 152 WITH B4 GID: ABBGXX

MANF: WAKEFIELD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.004	0.003		02.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.53	.02	.00	8H-70F- 6.5H-199F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00027.47	SEE MFG

66451 ADHESIVE DELTABOND 152 WITH C4

MANF: WAKEFIELD

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005198 4

66452 ADHESIVE DELTABOND 152 WITH D4
MANF: WAKEFIELD
....NO TEST DATA AVAILABLE....

66457 ADHESIVE DELTABOND 154 WITH A4
MANF: WAKEFIELD
....NO TEST DATA AVAILABLE....

66458 ADHESIVE DELTABOND 154 WITH B4
MANF: WAKEFIELD
....NO TEST DATA AVAILABLE....

66459 ADHESIVE DELTABOND 154 WITH C4
MANF: WAKEFIELD
....NO TEST DATA AVAILABLE....

66460 ADHESIVE DELTABOND 154 WITH D4
MANF: WAKEFIELD
....NO TEST DATA AVAILABLE....

66461 ADHESIVE DELTABOND 155
MANF: WAKEFIELD
....NO TEST DATA AVAILABLE....

66453 ADHESIVE DELTACAST 153 WITH A4
MANF: WAKEFIELD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.63	.02	.00	8H-70F- 96H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66454 ADHESIVE DELTACAST 153 WITH B4
MANF: WAKEFIELD
....NO TEST DATA AVAILABLE....

66455 ADHESIVE DELTACAST 153 WITH C4
MANF: WAKEFIELD
....NO TEST DATA AVAILABLE....

66456 ADHESIVE DELTACAST 153 WITH D4
MANF: WAKEFIELD
....NO TEST DATA AVAILABLE....

66223 ADHESIVE DENNISON A30
MANF: DENNISON MFG
....NO TEST DATA AVAILABLE....

66224 ADHESIVE DENNISON A40
MANF: DENNISON MFG
....NO TEST DATA AVAILABLE....

66225 ADHESIVE DENNISON A52
MANF: DENNISON MFG

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.61	.05	.88	168H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005199 6 ■

66226 ADHESIVE DENNISON A53
MANF: DENNISON MFG
....NO TEST DATA AVAILABLE....

66227 ADHESIVE DENNISON A70
MANF: DENNISON MFG
....NO TEST DATA AVAILABLE....

66228 ADHESIVE DENNISON A72
MANF: DENNISON MFG
....NO TEST DATA AVAILABLE....

66229 ADHESIVE DENNISON A73
MANF: DENNISON MFG
....NO TEST DATA AVAILABLE....

66230 ADHESIVE DENNISON C21
MANF: DENNISON MFG

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.53	.03	.53	24H-46F- 168H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66231 ADHESIVE DENNISON C37
MANF: DENNISON MFG
....NO TEST DATA AVAILABLE....

62334 ADHESIVE DENNISON GLUE STIC GID: ABXXXX
MANF: DENNISON MFG

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
X	00018.77	

TOXICITY

66232 ADHESIVE DENNISON M11
MANF: DENNISON MFG
....NO TEST DATA AVAILABLE....

66233 ADHESIVE DENNISON M12
MANF: DENNISON MFG
....NO TEST DATA AVAILABLE....

66234 ADHESIVE DENNISON M58
MANF: DENNISON MFG
....NO TEST DATA AVAILABLE....

66235 ADHESIVE DENNISON M9
MANF: DENNISON MFG
....NO TEST DATA AVAILABLE....

61081 ADHESIVE DENSIL 2078 SILICONE GID: ABCKXX
MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.004	0.003		02.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.78	.79	.00	

ODOR

RT	RT WEIGHT	CURE
A	K 00010.19	

TOXICITY

MSFC-HDBK-527 REV F ■ 9999942 0005200 9 ■

Information Handling Services, 2000

62542 ADHESIVE DENSIL SILICONE PS GID: AFCKXX
MANF: DENNISON MFG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	023.8	014.5	0.002	0.003		02.10		NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.94	.66	.00	

ODOR

RT	RT	WEIGHT	CURE
A	X	00008.51	24H-70F-

TOXICITY

62077 ADHESIVE DENSIL/KAPTON GID: AFCKXX
MANF: SHELDAHL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.2E-7	.92	.29		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

66929 ADHESIVE DEPEND 330
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

06161 ADHESIVE DEVCON 2-TON EPOXY WHITE GID: ABBGXX
MANF: DEVCON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
C	2	025.9	014.3	0.005	0.003	00.00	00.00		NONE
C	1	025.9	014.3	0.005	0.003	00.19	12.00	T	SMALL
B	2	025.9	014.3	0.001	0.003	00.00	00.00		NONE
B	1	025.9	014.3	0.001	0.003		07.00		NONE
A	1	030.0	009.0	0.001	0.003		04.60		NONE
I	1	033.0	014.3	0.001	0.003	00.62	12.00	T	NONE
X	2	100.0	020.2	0.005	0.003	00.30	12.00	T	NONE
X	1	100.0	020.2	0.005	0.003	01.78	12.00	T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	500	60	120	0.005	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	1.40	.08		24H-70F-
					24H-150F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00024.70	24H-70F-
			24H-150F-

TOXICITY

66236 ADHESIVE DEVCON 5-MINUTE EPOXY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66237 ADHESIVE DEVCON 5-MINUTE EPOXY GEL
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66238 ADHESIVE DEVCON ALUMINUM LIQUID 10710
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

65502 ADHESIVE DEVCON ALUMINUM PUTTY GID: ABXXXX
MANF: DEVCON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
B	2	023.8	014.3	0.010	0.003	00.00	00.00		NONE
B	1	023.8	014.3	0.010	0.003	00.20	08.10		NONE
B	1	030.0	010.0	0.010	0.003	00.20	11.10		NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	.83	.49	.10	24H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00022.46	24H-70F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005201 0

66239 ADHESIVE DEVCON ALUMINUM VERY LIQUID 11720
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66240 ADHESIVE DEVCON BACKING COMPOUND LIQUID 11915
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66241 ADHESIVE DEVCON BRONZE PUTTY 10260
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66242 ADHESIVE DEVCON BRUSHABLE CERAMIC COMPOUND 11760
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66243 ADHESIVE DEVCON CARBIDE PUTTY 10050
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66244 ADHESIVE DEVCON CERAMIC WEAR COMPOUND 11680
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

77247 ADHESIVE DEVCON DK40
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66246 ADHESIVE DEVCON EK1
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66248 ADHESIVE DEVCON EPOXY SEALER 100
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66249 ADHESIVE DEVCON FLOOR GRIP 13090
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66250 ADHESIVE DEVCON FLOOR PATCH 13100
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66251 ADHESIVE DEVCON H-TEMP CERAMIC PUTTY 11690
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66252 ADHESIVE DEVCON HI-TEMP MOLD MAKER 10370
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66265 ADHESIVE DEVCON LOCK-STUD LOCKING GRADE 19530
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005202 2

Information Handling Services, 2000

66266 ADHESIVE DEVCON LOCK-THREAD LOCKING PENETRANT-SUPER 18560
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66253 ADHESIVE DEVCON MVP TYPE II
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66254 ADHESIVE DEVCON PLASTIC/STEEL 5-MINUTE PUTTY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66255 ADHESIVE DEVCON PLASTIC/STEEL LIQUID 10210
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66256 ADHESIVE DEVCON PLASTIC/STEEL PUTTY 10110
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66257 ADHESIVE DEVCON PUMP REPAIR PUTTY 11700
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66245 ADHESIVE DEVCON RUBBER 14900
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66260 ADHESIVE DEVCON SPECIAL F EPOXY
MANF: DEVCON CORP

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.59	.04	.27	24H-46F-

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

62220 ADHESIVE DEVCON ST EPOXY GID: ABBGXX
MANF: DEVCON CORP

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	3.4E-6	.72	.06		24H-70F-
					24H-150F-

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

66261 ADHESIVE DEVCON STAINLESS STEEL PUTTY 10270
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66262 ADHESIVE DEVCON SUPER LOCK-NUT LOCKING GRADE 18520
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66263 ADHESIVE DEVCON SUPER LOCK-RETAINING GRADE 18540
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66268 ADHESIVE DEVCON TILE ADHESIVE
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005203 4

66269 ADHESIVE DEVCON TITANIUM PUTTY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66270 ADHESIVE DEVCON WET SURFACE REPAIR PUTTY 11800
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

84741 ADHESIVE DOLCHEM 3400
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

84743 ADHESIVE DOLCHEM 3420
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66394 ADHESIVE DOLCHEM 5072
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

84745 ADHESIVE DOLCHEM 6002
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66388 ADHESIVE DOLCHEM 6010
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

84748 ADHESIVE DOLCHEM 6016
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66389 ADHESIVE DOLCHEM 6021
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66390 ADHESIVE DOLCHEM 6029
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66391 ADHESIVE DOLCHEM 6034
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

84750 ADHESIVE DOLCHEM 6040
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

84751 ADHESIVE DOLCHEM 60466
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

84752 ADHESIVE DOLCHEM 6060
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005204 6 ■

Information Handling Services, 2000

DATE: 12/23/88
NON-METALS BY DESIGNATION

84753 ADHESIVE DOLCHEM 6065
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66392 ADHESIVE DOLCHEM 6067
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

84754 ADHESIVE DOLCHEM 6068
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66393 ADHESIVE DOLCHEM 6070
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66395 ADHESIVE DOLCHEM 6080
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66396 ADHESIVE DOLCHEM 6100
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66397 ADHESIVE DOLCHEM 6101
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

84755 ADHESIVE DOLCHEM 6109
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66398 ADHESIVE DOLCHEM 6110
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66399 ADHESIVE DOLCHEM 6111
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66400 ADHESIVE DOLCHEM 6115
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66401 ADHESIVE DOLCHEM 6116
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66402 ADHESIVE DOLCHEM 6121
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66403 ADHESIVE DOLCHEM 6126
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005205 8

Information Handling Services, 2000

66404 ADHESIVE DOLCHEM 6203
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66405 ADHESIVE DOLCHEM 6210
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66406 ADHESIVE DOLCHEM 6310/6311
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66407 ADHESIVE DOLCHEM 6420
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66408 ADHESIVE DOLCHEM 6488
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66409 ADHESIVE DOLCHEM 6529
MANF: DOLPHIN PAINT & CHEMICAL
....NO TEST DATA AVAILABLE....

66374 ADHESIVE DOLPHON CA1069
MANF: JOHN C DOLPH CO
....NO TEST DATA AVAILABLE....

66377 ADHESIVE DOLPHON CC1024A WITH RE2000
MANF: JOHN C DOLPH CO
....NO TEST DATA AVAILABLE....

66376 ADHESIVE DOLPHON CC1024A WITH RE2005
MANF: JOHN C DOLPH CO
....NO TEST DATA AVAILABLE....

66378 ADHESIVE DOLPHON CC1080
MANF: JOHN C DOLPH CO
....NO TEST DATA AVAILABLE....

66379 ADHESIVE DOLPHON CC1080L
MANF: JOHN C DOLPH CO
....NO TEST DATA AVAILABLE....

66380 ADHESIVE DOLPHON CC1096
MANF: JOHN C DOLPH CO
....NO TEST DATA AVAILABLE....

66381 ADHESIVE DOLPHON CC1099
MANF: JOHN C DOLPH CO
....NO TEST DATA AVAILABLE....

66382 ADHESIVE DOLPHON CC1105
MANF: JOHN C DOLPH CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005206 T

Information Handling Services, 2000

66383 ADHESIVE DOLPHON CC1126
MANF: JOHN C DOLPH CO
....NO TEST DATA AVAILABLE....

66384 ADHESIVE DOLPHON CC1129
MANF: JOHN C DOLPH CO
....NO TEST DATA AVAILABLE....

84728 ADHESIVE DOLPHON CH1119
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

66385 ADHESIVE DOLPHON CR1056-1
MANF: JOHN C DOLPH CO
....NO TEST DATA AVAILABLE....

66386 ADHESIVE DOLPHON CR1056-2
MANF: JOHN C DOLPH CO
....NO TEST DATA AVAILABLE....

65471 ADHESIVE DOUBLE/BUBBLE EPOXY GID: ABBGXX
MANF: HARDMAN INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	2.11	.08	.60	24H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

67255 ADHESIVE DP100 CLEAR
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67256 ADHESIVE DP105 CLEAR
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67257 ADHESIVE DP110 CLEAR
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.010	0.003	00.00	00.00	NONE
B	1	020.9	014.7	0.010	0.003	0.10	07.00	NONE
C	1	025.9	014.3	0.010	0.003	0.30	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	9.79	.07	.66	168H-70F-

ODOR

RT	RT WEIGHT	CURE
A	B 10.265	168H-70F-

TOXICITY

67258 ADHESIVE DP110 GRAY
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67259 ADHESIVE DP190 GRAY
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010	0.003		05.60	NONE
B	1	030.0	010.0	0.011	0.003	00.20	06.30	NONE
B	1	032.0	010.0	0.010	0.003	00.09	06.30	NONE
I	2	033.0	010.0	0.011	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005207 1

67259 ADHESIVE DP190 GRAY (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	1.91	.67	.51	168H-75F-

ODOR

RT	RT WEIGHT	CURE
A	B 22.398	168H-70F-

TOXICITY

60316 ADHESIVE DUCO GID: ABXXXX

MANF: DUCO

....NO TEST DATA AVAILABLE....

66412 ADHESIVE DUHESIVE SPRAY

MANF: DUBOIS CHEMICALS

....NO TEST DATA AVAILABLE....

67563 ADHESIVE DUR METAL SUPER-RAPID WEAR RESISTANT

MANF: 3M CO

....NO TEST DATA AVAILABLE....

65250 ADHESIVE DURALCO 700 HIGH TEMP GID: ABXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	015.0	0.078			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00010.30	

TOXICITY

66727 ADHESIVE DW24

MANF: GLIDDEN

....NO TEST DATA AVAILABLE....

65101 ADHESIVE DYMAX 181 GID: ABXXXX

MANF: AMERICAN CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	2.92	.03	1.79	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65104 ADHESIVE DYMAX 20017 GID: ABXXXX

MANF: AMERICAN CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	4.69	.02	1.15	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65103 ADHESIVE DYMAX 415 GID: ABXXXX

MANF: AMERICAN CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	3.72	.06	1.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65102 ADHESIVE DYMAX 602 GID: ABXXXX

MANF: AMERICAN CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	5.67	.06	2.40	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65303 ADHESIVE DYMAX 628 GID: ABXXXX

MANF: AMERICAN CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	6.11	.04	1.45	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005208 3

65676 ADHESIVE DYMAX 828 OIL/GRIP
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

65677 ADHESIVE DYMAX 832 OIL/GRIP
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

65679 ADHESIVE DYMAX 845 OIL/GRIP
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

65680 ADHESIVE DYMAX 847 OIL/GRIP
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

67611 ADHESIVE DYMAX 901
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

67612 ADHESIVE DYMAX 902
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

65616 ADHESIVE E-SOLDER 3012
MANF: ACME CHEMICALS & INSULATION CO
ALLIED PRODUCTS
....NO TEST DATA AVAILABLE....

65617 ADHESIVE E-SOLDER 3017
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

65618 ADHESIVE E-SOLDER 3021
MANF: ACME CHEMICALS & INSULATION CO

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	9.57	.19	.00	2H-149F- 3H-122F-	No test data		

65619 ADHESIVE E-SOLDER 3022
MANF: ACME CHEMICALS & INSULATION CO

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.25	.10	.00	24H-70F- 3H-149F- 1.5H-185F-	No test data		

65620 ADHESIVE E-SOLDER 3025
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

65621 ADHESIVE E-SOLDER 3026
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005209 5

65622 ADHESIVE E-SOLDER 3044
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

65623 ADHESIVE E-SOLDER 3056
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

65624 ADHESIVE E-SOLDER 3069
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

65625 ADHESIVE E-SOLDER 3083
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

65626 ADHESIVE E-SOLDER 320S
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

66757 ADHESIVE E1103
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66758 ADHESIVE E2001 A/B
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66759 ADHESIVE E2101 A/B
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66760 ADHESIVE E2102 A/B
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66761 ADHESIVE E2103 A/B
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66373 ADHESIVE E39
MANF: DIMITER EMULSION & CHEMICAL
....NO TEST DATA AVAILABLE....

66372 ADHESIVE E41
MANF: DIMITER EMULSION & CHEMICAL
....NO TEST DATA AVAILABLE....

66528 ADHESIVE E705
MANF: ETHERINGTON/U S PROLAM
....NO TEST DATA AVAILABLE....

66529 ADHESIVE E710
MANF: ETHERINGTON/U S PROLAM
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005210 1

Information Handling Services, 2000

66530 ADHESIVE E746
MANF: ETHERINGTON/U S PROLAM
....NO TEST DATA AVAILABLE....

66531 ADHESIVE E760
MANF: ETHERINGTON/U S PROLAM
....NO TEST DATA AVAILABLE....

66521 ADHESIVE E767
MANF: ETHERINGTON/U S PROLAM
....NO TEST DATA AVAILABLE....

60406 ADHESIVE EA1347 GID: ABXXXX
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

20369 ADHESIVE EA6 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.012	0.003		00.20	NONE
C	1	025.9	014.3	0.012	0.003	00.51	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	9.0E-7	2.27	.03		144H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00054.06	144H-70F-

20128 ADHESIVE EA8 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.014	0.003		00.10	NONE
C	1	025.9	014.3	0.014	0.003	00.40	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.98	.02	.00	1.5H-200F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00014.23	1.5H-200F-

60411 ADHESIVE EA815 GID: ABXXXX
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

61206 ADHESIVE EA828/DER732/AEP/CABOSIL GID: ABBGXX
MANF: HYSOL/DEXTER SPEC: HP 16-164

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.19	.92	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05686 ADHESIVE EA828/DTA/AL POWDER EPOXY GID: ABBGMA
MANF: HYSOL/DEXTER SPEC: PS 14030 COMP 2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.156	0.003		07.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

00005 ADHESIVE EA828/VERSAMID 115 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER SPEC: AB0130-010-C3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.010	0.003		03.70	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005211 3

00005 ADHESIVE EA828/VERSAMID 115 EPOXY (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	V	00030.18	2H-70F- 24H-150F-

05604 ADHESIVE EA828/VERSAMID 125/FILLED GID: ABBGMI

MANF: HYSOL/DEXTER SPEC: PS 14032 TY1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.110	0.003		03.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.06	.02		16H-180F-0psiaVACUUM

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

05132 ADHESIVE EA828/VERSAMID 140 1/1BW GID: ABXXXX

MANF: HYSOL/DEXTER
SHELL CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.010	0.003	00.00	00.00	NONE
X	1	030.0	010.0	0.010	0.003		08.70	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.30	.05	.00	168H-415F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

66326 ADHESIVE EA901/A1

MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.82	.03	.01	12H-46F- 16H-122F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

06132 ADHESIVE EA901/B1 GID: ABBGXX

MANF: HYSOL/DEXTER SPEC: MMM-A-132

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.007	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.007	0.003	00.50	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	1.40	.00	.65	1H-200F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	B	00020.60	24H-70F-

66327 ADHESIVE EA901/L3

MANF: HYSOL/DEXTER

....NO TEST DATA AVAILABLE....

84531 ADHESIVE EA901NA/B1

MANF: HYSOL/DEXTER

....NO TEST DATA AVAILABLE....

66343 ADHESIVE EA901NA/L3

MANF: HYSOL/DEXTER

....NO TEST DATA AVAILABLE....

66328 ADHESIVE EA911F

MANF: HYSOL/DEXTER

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005212 5

60065 ADHESIVE EA913 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	22.72	.06	.00	2H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

85489 ADHESIVE EA913NA
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

06587 ADHESIVE EA919 A/B EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.34	.02	.00	336H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66329 ADHESIVE EA919/L3 GID: ABBGXX
MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.009	0.006	00.16	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
V	29.44	

TOXICITY

69919 ADHESIVE EA9210H PR 10% GID: ABXXXX
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

69920 ADHESIVE EA9210H PR 5% GID: ABXXXX
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

80062 ADHESIVE EA921NA EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.42	.03	.00	2H-160F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

85369 ADHESIVE EA9228 PRIMER
MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		01.25	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05881 ADHESIVE EA926 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66330 ADHESIVE EA929
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66331 ADHESIVE EA9306
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005213 7

06452 ADHESIVE EA9307 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.48	.00	.00	.5H-121F- 2H-180F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05192 ADHESIVE EA9309 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.006	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.006	0.003		02.50	NONE
X	1	025.9	014.3	0.021	0.003	00.32	12.00	T MOD
X	1	030.0	009.0	0.014	0.003	00.24	12.00	T MOD
X	1	030.0	010.0	0.013	0.003	00.60	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.25	.00	.00	168H-70F- 5H-165F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
B	00022.60	72H-70F-

66332 ADHESIVE EA9309-2
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66333 ADHESIVE EA9309-3NA
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

06609 ADHESIVE EA9320NA EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	030.0	010.0	0.010	.010		00.00	NONE
A		30.0	10.0	.010	.010		00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.12	.04	.00	.25H-250F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	V 22.387	168H-70F-

05289 ADHESIVE EA9321 EPOXY GID: ABAKXX
MANF: HYSOL/DEXTER

SPEC: MB0120-027T2 MB0120-037T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.015		00.00	00.00	NONE
C	1	025.9	014.3	0.015		00.52	12.00	T NONE
I	1	030.0	009.0	0.015	0.003	00.33	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.45	.00	.00	24H-46F- 2H-151F- 24H-151F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

66334 ADHESIVE EA9323
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005214 9

63728 ADHESIVE EA9326 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.4E-6	17.13	11.56	.40	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62718 ADHESIVE EA9330 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER
SPEC: STM0737

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.020	0.003		03.00	MOD
X	1	025.9	014.3	0.020	0.003		03.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	2.00	.04	.51	24H-70F-

ODOR

RT	RT WEIGHT	CURE
X	00061.76	

TOXICITY

85521 ADHESIVE EA934 EPOXY GID: ABBGXX
MANF: HYSOL DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.050		00.02	12.00	T MOD
X	1	025.9	014.3	0.012	0.003	00.48	12.00	T MOD
X	1	030.0	009.0	0.049	0.003	00.03	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	00.85	00.00		

ODOR

RT	RT WEIGHT	CURE
B	00038.00	168H-70F-

TOXICITY

00007 ADHESIVE EA934NA EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER
SPEC: MB0120-008

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.077		00.00	00.00	NONE
A	1	030.0	009.0	0.076		00.00	00.00	NONE
A	1	100.0	020.2	0.078			00.10	NONE

FSC

RT	FLUID NAME
No test data	

RT

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	00.49	00.01	00.00	168H-70F-

ODOR

RT	RT WEIGHT	CURE
A	B 00020.57	2H-200F-

TOXICITY

66335 ADHESIVE EA9351
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

20211 ADHESIVE EA940 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER
SPEC: MIL-A-8623

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.008	0.003		00.50	NONE
C	1	025.9	014.3	0.008	0.003	00.30	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.87	.21		16H-150F-

ODOR

RT	RT WEIGHT	CURE
X	00021.00	344H-70F-

TOXICITY

60764 ADHESIVE EA9414 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.78	.14	.00	SEE TEST REPORT

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005215 0

05915 ADHESIVE EA9421 GID: ABAKXX
MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.010	0.003	00.00	00.00	NONE
B	1	023.8	014.5	0.010	0.003		10.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.4E-7	5.41	.63		24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00010.56	24H-150F-

60200 ADHESIVE EA946 GID: ABXXXX
MANF: HYSOL/DEXTER SPEC: STW5-2931 UF-3262
....NO TEST DATA AVAILABLE....

66344 ADHESIVE EA946/L3-2
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

05374 ADHESIVE EA956 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER SPEC: LAC30-4745-0100

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.006	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.006	0.003		02.60	NONE
A	1	023.8	014.5	0.007	0.003		03.70	NONE
X	1	025.9	014.3	0.020	0.003	00.04	10.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.8E-6	1.76	.01		168H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00030.37	1H-200F- 168H-70F- 24H-150F-

66337 ADHESIVE EA960
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

05139 ADHESIVE EA9601 EPOXY GID: ABBGXX
MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.014	0.003		02.10	NONE
A	1	030.0	009.0	0.010	0.003		02.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.55	.45	.00	1H-250F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00039.44	1H-250F-

66336 ADHESIVE EA960F
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

61300 ADHESIVE EA9628NW FILM GID: ACXXXX
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.90	.00	.00	3H-259F- 24H-284F-0psiaVACUUM

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005216 2

66346 ADHESIVE EA9814NA
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

00591. ADHESIVE EASTMAN 901 GID: ABXXXX
MANF: EASTMAN KODAK
SPEC: MIL-A-46050

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.93	.02		

ODOR

RT	RT WEIGHT	CURE
A	B 00007.23	24H-70F-

TOXICITY

66163 ADHESIVE EASYPOXY K20
MANF: CONAP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.55	.02	.00	4H-122F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66164 ADHESIVE EASYPOXY K22
MANF: CONAP
....NO TEST DATA AVAILABLE....

66165 ADHESIVE EASYPOXY K23A
MANF: CONAP
....NO TEST DATA AVAILABLE....

66166 ADHESIVE EASYPOXY K256
MANF: CONAP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.60	.04	.00	24H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66167 ADHESIVE EASYPOXY K26
MANF: CONAP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.11	.05	.00	2H-151F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66168 ADHESIVE EASYPOXY K40
MANF: CONAP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.60	.02	.00	24H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66169 ADHESIVE EASYPOXY K45
MANF: CONAP
....NO TEST DATA AVAILABLE....

60975 ADHESIVE EC1022 GID: ABHDXX
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	V 00005.04	24H-70F-

TOXICITY

83642 ADHESIVE EC1137
MANF: 3M CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005217 4

Information Handling Services, 2000

83643 ADHESIVE EC1239 B/A CLASS A 1/2
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83644 ADHESIVE EC1239 B/A CLASS A 1/4
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83645 ADHESIVE EC1239 B/A CLASS A 2
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83646 ADHESIVE EC1239 B/A CLASS A 4
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83647 ADHESIVE EC1239 B/A CLASS B 1/2
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83648 ADHESIVE EC1239 B/A CLASS B 1/4
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83649 ADHESIVE EC1239 B/A CLASS B 2
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83650 ADHESIVE EC1239 B/A CLASS B 4
MANF: 3M CO
....NO TEST DATA AVAILABLE....

20198 ADHESIVE EC1357 NEOPRENE CEMENT GID: ABDBXX
MANF: 3M CO SPEC: MIL-A-21366

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.017		00.00	00.00	NONE
A	1	020.9	014.7	0.017			05.00	SMALL
A	1	025.9	014.3	0.004	0.003		04.50	NONE
A	1	033.0	014.3	0.004	0.003		02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.48	.90	.00	24H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00001.78	24H-70F-
		24H-150F-

67346 ADHESIVE EC1386
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83652 ADHESIVE EC1547 B/A
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67345 ADHESIVE EC1828
MANF: 3M CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005218 6

61214 ADHESIVE EC1945 A/B GID: AGXXXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	X	00007.22	24H-70F-
			168H-70F-

TOXICITY

20081 ADHESIVE EC2158 EPOXY GID: ABBGXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003		02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05649 ADHESIVE EC2290 EPOXY GID: AUBGXX
MANF: 3M CO
SPEC: MB0120-090

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.004	0.003		01.80	NONE
A	1	030.0	010.0	0.003	0.003		01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.98	.01	.00	2H-358F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00005.04	.5H-200F-

TOXICITY

69626 ADHESIVE EC3430
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67350 ADHESIVE EC3500 B/A
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.20	.07	.00	1H-250F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60713 ADHESIVE EC3549 A/B POLYURETHANE GID: ABXXXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.250			02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.2E-6	1.17	.02	.65	24H-70F-
					24H-150F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

67355 ADHESIVE EC3569 B/A
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.010	0.003	00.07	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	2.03	.00	.70	168H-75F-

ODOR

RT	RT	WEIGHT	CURE
A	B	20.830	168H-75F-

TOXICITY

67349 ADHESIVE EC3903
MANF: 3M CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005219 8

61314 ADHESIVE EC3924 GID: ABXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.07	.08		4H-250F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06462 ADHESIVE EC4500 CHLORINATED ELAST GID: ABDEXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.006	0.003	00.00	00.00	NONE
X	1	025.9	014.3	0.006	0.003		11.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.8E-6	6.47	2.73	.07	.17H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
X	00006.41	.17H-70F- 24H-150F-

TOXICITY

05429 ADHESIVE EC776 GID: ABDJXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.010	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.010	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	X 00000.76	16H-70F- 24H-146F-

TOXICITY

06325 ADHESIVE EC847 NITRILE BASED GID: ABDJXX

MANF: HYSOL/DEXTER

....NO TEST DATA AVAILABLE....

05745 ADHESIVE ECCOBOND 104 EPOXY GID: ABBGXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.068			01.00	SMALL
A	1	035.0	009.0	0.082			02.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.33	.07		6H-250F-

ODOR

RT	RT WEIGHT	CURE
A	V 00008.35	6H-250F-

TOXICITY

05943 ADHESIVE ECCOBOND 104/ALUMINA GID: BAXXXX

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.43	.00	.00	2H-350F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66276 ADHESIVE ECCOBOND 144B

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

66277 ADHESIVE ECCOBOND 1760

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

66278 ADHESIVE ECCOBOND 1765

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005220 4

06076 ADHESIVE ECCOBOND 24 GID: ABBGXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003	0.003		03.70	NONE
X	1	030.0	009.0	0.050		00.21	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.13	.02	.00	24H-70F- 24H-176F-0psiaVACUUM

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	21.965	

66279 ADHESIVE ECCOBOND 26

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

66280 ADHESIVE ECCOBOND 27

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

66281 ADHESIVE ECCOBOND 276 GID: AEBGGS

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

05857 ADHESIVE ECCOBOND 276/C17 GID: AEBGGS

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.50	.01	.00	2H-176F- 1H-302F- 2H-392F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

66282 ADHESIVE ECCOBOND 281

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.35	.06	.00	5H-176F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

66283 ADHESIVE ECCOBOND 285-1

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

66284 ADHESIVE ECCOBOND 285-2

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

66285 ADHESIVE ECCOBOND 285-3

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

05475 ADHESIVE ECCOBOND 285/11 EPOXY GID: ABBGXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.016	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.016	0.003		02.70	NONE
A	1	023.8	014.5	0.017	0.003		01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00055.76	2H-250F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005221 6

05475 ADHESIVE ECCOBOND 285/11 EPOXY (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR

RT	RT WEIGHT	CURE
		8H-180F-

TOXICITY

05608 ADHESIVE ECCOBOND 285/24LV EPOXY GID: ABBGXX

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	1.00	.01	.00	24H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66286 ADHESIVE ECCOBOND 3-2-5C

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

66287 ADHESIVE ECCOBOND 45

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

05178 ADHESIVE ECCOBOND 45/C15 GID: ABBGXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.008	0.003		04.10	NONE
X	2	100.0	022.0	0.020	0.003	00.20	12.00	T MOD
X	1	100.0	022.0	0.020	0.003	01.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.92	.07	.00	.5H-219F-

ODOR

RT	RT WEIGHT	CURE
A	X 00020.13	2H-70F-
		1H-212F-

TOXICITY

66288 ADHESIVE ECCOBOND 45LV

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

66289 ADHESIVE ECCOBOND 51

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.08	.02	.46	24H-46F-
					168H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61155 ADHESIVE ECCOBOND 51/C11 GID: ABBGXX

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-7	.42	.00		48H-250F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

00934 ADHESIVE ECCOBOND 51/C9 EPOXY GID: ABBGXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	009.0	0.045	0.003	00.11	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.74	.02	.49	2H-150F-

ODOR

RT	RT WEIGHT	CURE
A	B 00038.06	24H-70F-
		24H-150F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005222 8

05036 ADHESIVE ECCOBOND 55/C9 GID: ABBGXX
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.43	.43	.00	24H-302F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

60846 ADHESIVE ECCOBOND 56/C11 GID: ABBGIA
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.8E-7	.06	.02		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05600 ADHESIVE ECCOBOND 56C EPOXY GID: ABBGMR
MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.005	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.005	0.003		02.50	NONE
A	1	030.0	009.0	0.004	0.003		01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.18	.00	.00	4H-140F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00033.46	2H-150F-

20088 ADHESIVE ECCOBOND 56C/C9 GID: ABBGXX
MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003		01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.23	.01	.00	.5H-70F-
					1H-140F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00011.76	2H-120F-

06165 ADHESIVE ECCOBOND 59C/C59C GID: ABCKMR
MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.025	0.003		02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.2E-6	.12	.06		6H-300F-
					16H-400F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	B 00020.41	2H-70F-
		6H-300F-

66299 ADHESIVE ECCOBOND 60C
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

60112 ADHESIVE ECCOBOND 60L GID: ABXXXX
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.77	.11	.00	16H-46F-
					48H-122F-0psiaVACUUM

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

66290 ADHESIVE ECCOBOND 64C
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005223 T

66291 ADHESIVE ECCOBOND 64C1
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

06015 ADHESIVE ECCOBOND 66C EPOXY GID: ABBGXX
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.30	.01	.22	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05752 ADHESIVE ECCOBOND 70C EPOXY GID: ABBGXX
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

05813 ADHESIVE ECCOBOND 787 A/B EPOXY GID: ABBGXX
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.83	.04	2.06	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

65512 ADHESIVE ECCOBOND 83C EPOXY GID: ABBGXX
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.64	.02	.00	1H-151F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	00003.42	

66295 ADHESIVE ECCOBOND 87H(NF)
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.51	.03	.00	24H-149F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

66296 ADHESIVE ECCOBOND 91/C11
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

66297 ADHESIVE ECCOBOND 91/C23LV
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

66298 ADHESIVE ECCOBOND 91/C9
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

66300 ADHESIVE ECCOBOND SF40
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.24	.04	.00	48H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

06143 ADHESIVE ECCOBOND SOLDER 57C GID: ABBGXX
MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.005	0.003		02.30	NONE
C	1	033.0	014.3	0.011	0.003	00.94	12.00	T NONE
X	1	100.0	016.5	0.005	0.003	01.25	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005224 1

06143 ADHESIVE ECCOBOND SOLDER 57C (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.67	.06	.00	16H-126F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	B	00075.27	24H-70F- 24H-150F-

20089 ADHESIVE ECCOBOND SOLDER 58 GID: ABBGXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.007	0.003		02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.37	.17	.00	2H-300F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	B	00029.51	2H-300F-

60768 ADHESIVE ECCOBOND SOLDER V91 GID: ABBGXX

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.91	.00	.00	24H-46F- 24H-199F- 24H-199F-0psiaVACUUM

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

60430 ADHESIVE ECCOFOAM EFF14 GID: ABBGXX

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.40	.09	.00	24H-212F- 24H-257F-0psiaVACUUM

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	V	00009.75	116H-185F-

06564 ADHESIVE ECCOFOAM FPH12-4H GID: ABBGXX

MANF: EMERSON AND CUMING SPEC: MB0130-137/T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.271		00.02	12.00	T NONE
X	1	020.9	014.7	0.271		00.60	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.72	.10	.00	24H-248F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

84439 ADHESIVE ECCOLITE 82EP-PB

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

84440 ADHESIVE ECCOLITE 82SI-RS

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

20195 ADHESIVE ECCOPRIME S11 GID: AUXXXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.001	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	B	00084.53	24H-70F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005225 3

84448 ADHESIVE ECCOSHIELD VY-NC
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.58	.32	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

84449 ADHESIVE ECCOSHIELD VY-NN
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84447 ADHESIVE ECCOSHIELD VY81
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84450 ADHESIVE ECCOSIL 1745
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84451 ADHESIVE ECCOSIL 4553 RUBBER
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84452 ADHESIVE ECCOSIL 4640
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.03	.28	.00	16H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

20472 ADHESIVE ECCOSIL 4712 GID: ABBGXX
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84453 ADHESIVE ECCOSIL 4850
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.28	.35	.00	16H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

20822 ADHESIVE ECCOSIL 4952 GID: ABCKXX
MANF: EMERSON AND CUMING SPEC: MB0120-089

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.010	0.003		00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.2E-6	.41	.09	.04	216H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
V	00057.50	

60425 ADHESIVE ECCOSIL 4952/50 GID: ABCKXX
MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010	0.003		01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.48	.14	.40	2H-176F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005226 5

84454 ADHESIVE ECCOSIL GEL
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84455 ADHESIVE ECCOSIL TP50
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.56	.83	2.49	16H-158F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05912 ADHESIVE ECCOSIL W191C11/S11 GID: BABGXX
MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		03.80	NONE
B	1	033.0	014.3	0.004	0.003	00.32	08.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-7	.71	.00		16H-170F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A B	00019.98	16H-170F-

05348 ADHESIVE ECCOSORB CR3 IRON/SILICONE RUBBER GID: DOCKXX
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.20	.08	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

66301 ADHESIVE ECCOSORB MF-S
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

06164 ADHESIVE ECCOSORB MF-S124 GID: ABBGXX
MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.250		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-7	.19	.06	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

06333 ADHESIVE ECCOSORB RF/HT99 GID: ABBGXX
MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	3.000			00.10	SMALL
A	1	020.9	014.7	2.900			00.60	NONE
A	1	025.9	014.3	3.000			00.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.50	.77	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

06332 ADHESIVE ECCOSORB VHP GID: ABBGXX
MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	3.100		02.09	08.40 T	NONE
X	1	020.9	014.7	3.100		01.72	11.80 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005227 7

84658 ADHESIVE ECN1235/906/MBDMA
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84700 ADHESIVE ECN1235/907/066
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84702 ADHESIVE ECN1235/BF3MEA
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84704 ADHESIVE ECN1273/906/MBDMA
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84707 ADHESIVE ECN1299/906
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84330 ADHESIVE ECN1299/906/MNDMA
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

69627 ADHESIVE ECP3446
MANF: 3M CO
....NO TEST DATA AVAILABLE....

66599 ADHESIVE ECR4100
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

66600 ADHESIVE ECR4200
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

66601 ADHESIVE ECR4300
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

66598 ADHESIVE ECR4700
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

66762 ADHESIVE EE1102
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

64875 ADHESIVE EE4215/H3469 GID: ABBGXX
MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.080			00.12	NONE
X	1	030.0	010.0	0.080		00.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00022.70	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005228 9

66763 ADHESIVE EL2705
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

06491 ADHESIVE ELASTOMERIC PROPRIETARY GID: ABBMXX
MANF: DEUTSCH

THERMAL VACUUM STABILITY						ODOR		TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE	
A	1.0E-6	.27	.00	.00		No test data			

66369 ADHESIVE EMBOND 747
MANF: DIMITER EMULSION & CHEMICAL
....NO TEST DATA AVAILABLE....

66368 ADHESIVE EMPLAST 560
MANF: DIMITER EMULSION & CHEMICAL
....NO TEST DATA AVAILABLE....

20359 ADHESIVE EMX138 A/B GID: ABXXXX
....NO TEST DATA AVAILABLE....

81121 ADHESIVE EP11C
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81122 ADHESIVE EP12
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81123 ADHESIVE EP13
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

66916 ADHESIVE EP1300 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

66917 ADHESIVE EP1330 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

66907 ADHESIVE EP1350 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

66908 ADHESIVE EP1500 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81126 ADHESIVE EP21
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81128 ADHESIVE EP21AO
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005229 0

81129 ADHESIVE EP21CLV
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81130 ADHESIVE EP21D
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81131 ADHESIVE EP21HV
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81132 ADHESIVE EP21LP
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81133 ADHESIVE EP21LV
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81134 ADHESIVE EP21M
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81135 ADHESIVE EP22
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81136 ADHESIVE EP23
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81137 ADHESIVE EP24
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81139 ADHESIVE EP25
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81141 ADHESIVE EP26
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81143 ADHESIVE EP28
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81145 ADHESIVE EP28M
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81146 ADHESIVE EP3
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005230 7

81147 ADHESIVE EP30
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81148 ADHESIVE EP30C
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81149 ADHESIVE EP30D7
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81150 ADHESIVE EP30DP4X2
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81153 ADHESIVE EP30DP8
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81154 ADHESIVE EP30DP8LV
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81156 ADHESIVE EP30HT
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81157 ADHESIVE EP30M1
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81161 ADHESIVE EP30S1
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

66901 ADHESIVE EP3200 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

66904 ADHESIVE EP3203 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

66902 ADHESIVE EP3230 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

66903 ADHESIVE EP3250 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

66913 ADHESIVE EP3280 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005231 9

66915 ADHESIVE EP3281 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

66905 ADHESIVE EP3285 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81163 ADHESIVE EP33
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

66909 ADHESIVE EP3351 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81165 ADHESIVE EP33CLV
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81166 ADHESIVE EP33LV
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81168 ADHESIVE EP34
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81170 ADHESIVE EP34LV
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81171 ADHESIVE EP35
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

66899 ADHESIVE EP3500 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

66900 ADHESIVE EP3501 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81174 ADHESIVE EP35CLV
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

66910 ADHESIVE EP3641
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

66911 ADHESIVE EP3642
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005232 0 ■

Information Handling Services, 2000

66912 ADHESIVE EP3652
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

66914 ADHESIVE EP3680
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

66906 ADHESIVE EP3685
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81175 ADHESIVE EP3AO
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81176 ADHESIVE EP3HTFLM4
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81177 ADHESIVE EP3HTHD
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81178 ADHESIVE EP3T
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81179 ADHESIVE EP4
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81182 ADHESIVE EP45
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81183 ADHESIVE EP45H
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81185 ADHESIVE EP5
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81186 ADHESIVE EP51
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81188 ADHESIVE EP51FL
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81190 ADHESIVE EP51HT
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005233 2

Information Handling Services, 2000

81192 ADHESIVE EP51M
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81193 ADHESIVE EP51T
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81194 ADHESIVE EP62
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81195 ADHESIVE EP62M
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81196 ADHESIVE EP72
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81197 ADHESIVE EP72AO
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81199 ADHESIVE EP72M3
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81200 ADHESIVE EP73
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81201 ADHESIVE EP74
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81202 ADHESIVE EP75
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81204 ADHESIVE EP76
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81206 ADHESIVE EP76M
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81207 ADHESIVE EP76M1
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81209 ADHESIVE EP76M1A
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005234 4

Information Handling Services, 2000

81212 ADHESIVE EP76M1R
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81213 ADHESIVE EP76MF
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81216 ADHESIVE EP76MHP
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81217 ADHESIVE EP76MHT
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81219 ADHESIVE EP76MHTHP
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81221 ADHESIVE EP77
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81222 ADHESIVE EP77M
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81224 ADHESIVE EP77M1
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81226 ADHESIVE EP77M1HP
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81229 ADHESIVE EP77MF
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81230 ADHESIVE EP8
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81232 ADHESIVE EP9
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

66637 ADHESIVE EPIBOND 104 A/B
MANF: FURANE
....NO TEST DATA AVAILABLE....

06270 ADHESIVE EPIBOND 115 EPOXY GID: ABBGXX
MANF: FURANE

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.003	0.003		03.60	NONE	No test data		No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005235 6

06270 ADHESIVE EPIBOND 115 EPOXY (cont)

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	%REACT	%TEST
A	1	030.0	010.4	0.003	0.003		03.50	NONE									

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	11.63	.49	.00	16H-77F- 16H-257F-

ODOR		TOXICITY	
RT	RT	WEIGHT	CURE
A	B	00020.61	.5H-212F- 12H-70F-

60354 ADHESIVE EPIBOND 1210/9615A EPOXY

MANF: M & T CHEMICALS SPEC: LAC30-4639-0100

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.69	.00	.00	48H-46F-

ODOR		TOXICITY	
RT	RT	WEIGHT	CURE
No test data			

66686 ADHESIVE EPIBOND 1210A/9610

MANF: FURANE

....NO TEST DATA AVAILABLE....

66703 ADHESIVE EPIBOND 1210A/9615-10

MANF: FURANE

....NO TEST DATA AVAILABLE....

66687 ADHESIVE EPIBOND 1210A/9615-62

MANF: FURANE

....NO TEST DATA AVAILABLE....

66638 ADHESIVE EPIBOND 1210A/9861

MANF: FURANE

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.77	.00	.00	168H-70F-

ODOR		TOXICITY	
RT	RT	WEIGHT	CURE
No test data			

06523 ADHESIVE EPIBOND 1210A/C1210B GID: ABBGXX

MANF: M & T CHEMICALS

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	%REACT	%TEST
X	2	025.9	014.3	0.014	0.003	00.00	00.00	NONE	No test data		No test data						
X	1	025.9	014.3	0.014	0.003	00.14	12.00	T MOD									

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	2.31	1.49	.00	

ODOR		TOXICITY	
RT	RT	WEIGHT	CURE
A	B	00024.48	48H-70F-

66639 ADHESIVE EPIBOND 1217 A/B

MANF: FURANE

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.59	.03	.43	SEE TEST REPORT

ODOR		TOXICITY	
RT	RT	WEIGHT	CURE
No test data			

66640 ADHESIVE EPIBOND 1218 A/B

MANF: FURANE

....NO TEST DATA AVAILABLE....

01175 ADHESIVE EPIBOND 123/931 EPOXY GID: ABBGXX

MANF: FURANE

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.17	.02	.00	16H-150F-

ODOR		TOXICITY	
RT	RT	WEIGHT	CURE
No test data			

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005236 8

66641 ADHESIVE EPIBOND 126 A/B
MANF: FURANE
....NO TEST DATA AVAILABLE....

66699 ADHESIVE EPIBOND 1337
MANF: FURANE
....NO TEST DATA AVAILABLE....

66642 ADHESIVE EPIBOND 1337/9514A
MANF: FURANE
....NO TEST DATA AVAILABLE....

66643 ADHESIVE EPIBOND 1337/9615A
MANF: FURANE
....NO TEST DATA AVAILABLE....

66698 ADHESIVE EPIBOND 1526
MANF: FURANE
....NO TEST DATA AVAILABLE....

66644 ADHESIVE EPIBOND 153 A/B
MANF: FURANE
....NO TEST DATA AVAILABLE....

66645 ADHESIVE EPIBOND 1534 A/B
MANF: FURANE
....NO TEST DATA AVAILABLE....

69798 ADHESIVE EPIBOND 1537
MANF: 3M CO
FURANE

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.008	0.003		05.25	MOD	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	26.04	

66696 ADHESIVE EPIBOND 1539
MANF: FURANE
....NO TEST DATA AVAILABLE....

66646 ADHESIVE EPIBOND 1543 A/B
MANF: FURANE

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	1.0E-6	.97	.46	.00	120H-46F-	No test data			

66694 ADHESIVE EPIBOND 1544
MANF: FURANE
....NO TEST DATA AVAILABLE....

66693 ADHESIVE EPIBOND 1545
MANF: FURANE
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005237 T

66692 ADHESIVE EPIBOND 1546
MANF: FURANE
....NO TEST DATA AVAILABLE....

66691 ADHESIVE EPIBOND 1547
MANF: FURANE
....NO TEST DATA AVAILABLE....

66690 ADHESIVE EPIBOND 1548
MANF: FURANE
....NO TEST DATA AVAILABLE....

66647 ADHESIVE EPIBOND 156 A/B
MANF: FURANE
....NO TEST DATA AVAILABLE....

60189 ADHESIVE EPIBOND 156/956 GID: ABBGXX
MANF: FURANE
....NO TEST DATA AVAILABLE....

66648 ADHESIVE EPIBOND 7000 A/B
MANF: FURANE
....NO TEST DATA AVAILABLE....

66649 ADHESIVE EPIBOND 7001 A/B
MANF: FURANE
....NO TEST DATA AVAILABLE....

66650 ADHESIVE EPIBOND 7002
MANF: FURANE
....NO TEST DATA AVAILABLE....

66651 ADHESIVE EPIBOND 7004
MANF: FURANE
....NO TEST DATA AVAILABLE....

66652 ADHESIVE EPIBOND 7100 A/B
MANF: FURANE
....NO TEST DATA AVAILABLE....

66653 ADHESIVE EPIBOND 7102
MANF: FURANE
....NO TEST DATA AVAILABLE....

66654 ADHESIVE EPIBOND 7103
MANF: FURANE
....NO TEST DATA AVAILABLE....

66655 ADHESIVE EPIBOND 7200
MANF: FURANE
....NO TEST DATA AVAILABLE....

66657 ADHESIVE EPIBOND 7202
MANF: FURANE
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005238 1

Information Handling Services, 2000

66658 ADHESIVE EPIBOND 7300
MANF: FURANE
....NO TEST DATA AVAILABLE....

66659 ADHESIVE EPIBOND 7301
MANF: FURANE
....NO TEST DATA AVAILABLE....

66660 ADHESIVE EPIBOND 7375
MANF: FURANE
....NO TEST DATA AVAILABLE....

05146 ADHESIVE EPIBOND 8287 EPOXY GID: ABBGXX
MANF: FURANE SPEC: MB0120-040T3
....NO TEST DATA AVAILABLE....

66661 ADHESIVE EPIBOND 8543 A/B
MANF: FURANE
....NO TEST DATA AVAILABLE....

05563 ADHESIVE EPIBOND 87399 EPOXY GID: ABBGXX
MANF: FURANE SPEC: MB0120-008

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	%REACT	%TEST
C	2	023.8	014.5	0.025			00.40	NONE	No test data		No test data					
C	1	023.8	014.5	0.025		00.42	11.50	T NONE								

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	.85	.02		

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	A	00068.73	

66662 ADHESIVE EPIBOND 87680
MANF: FURANE
....NO TEST DATA AVAILABLE....

66663 ADHESIVE EPIBOND 87803
MANF: FURANE
....NO TEST DATA AVAILABLE....

66664 ADHESIVE EPIBOND 88434
MANF: FURANE
....NO TEST DATA AVAILABLE....

66683 ADHESIVE EPIBOND 88807
MANF: FURANE
....NO TEST DATA AVAILABLE....

05191 ADHESIVE EPIBOND X8733C EP/AG FIL GID: ABBGMR
MANF: FURANE

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	%REACT	%TEST
C	2	023.8	014.5	0.010	0.003	00.00	00.00	NONE	No test data		No test data					
C	1	023.8	014.5	0.010	0.003	00.40	12.00	T NONE								
B	2	023.8	014.5	0.009	0.003	00.00	00.00	NONE								
B	1	023.8	014.5	0.009	0.003		06.70	NONE								

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	2.56	1.01	.00	

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	B	00049.57	24H-150F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005239 3

67163 ADHESIVE EPIC 0104
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

67162 ADHESIVE EPIC 701
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

67164 ADHESIVE EPIC R1011
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

67165 ADHESIVE EPIC R103D
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

67166 ADHESIVE EPIC R2027
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

67167 ADHESIVE EPIC R3500
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

67168 ADHESIVE EPIC S7002
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

62079 ADHESIVE EPIPHEN 825A EPOXY GID: ABBGXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.90	.01	.58	2H-176F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

67092 ADHESIVE EPIPHEN 825B
MANF: MONOMER-POLYMER AND DAJAC LABS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.10	.02	.00	3H-176F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05709 ADHESIVE EPIREZ 510 GID: ABBGXX
MANF: CELANESE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.006	0.003		03.30	SMALL
A	1	023.8	014.5	0.009	0.003		03.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.0E-7	.61	.01		4H-95F- 6H-185F-

ODOR

RT	RT WEIGHT	CURE
A	B 00038.11	4H-95F- 6H-185F-

TOXICITY

65948 ADHESIVE EPISEAL 10-10
MANF: BONDED PRODUCTS
....NO TEST DATA AVAILABLE....

60942 ADHESIVE EPISEAL 20-20 EPOXY GID: ABBGXX
MANF: BONDED PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010	0.003		05.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
I	MECH	100	72	70	0.007	00	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005240 T

60942 ADHESIVE EPISEAL 20-20 EPOXY (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.010	0.003		05.20	NONE
X	1	100.0	020.2	0.024	0.003	00.96	12.00	MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
I	PNEU	100		70	0.014	00	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.08	.31	.00	24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00021.02	24H-70F- 24H-150F-

65949 ADHESIVE EPISEAL 5 MINUTE EPOXY
MANF: BONDED PRODUCTS
....NO TEST DATA AVAILABLE....

65950 ADHESIVE EPISEAL IRON PUTTY
MANF: BONDED PRODUCTS
....NO TEST DATA AVAILABLE....

65947 ADHESIVE EPISEAL PLUS
MANF: BONDED PRODUCTS
....NO TEST DATA AVAILABLE....

84331 ADHESIVE EPN1139/HT907/DY062
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

66132 ADHESIVE EPO 114 GEL
MANF: COMMERCIAL CHEMICAL
....NO TEST DATA AVAILABLE....

66134 ADHESIVE EPO 114 T2 LIQUID
MANF: COMMERCIAL CHEMICAL
....NO TEST DATA AVAILABLE....

66133 ADHESIVE EPO 114 TI LIQUID
MANF: COMMERCIAL CHEMICAL
....NO TEST DATA AVAILABLE....

66135 ADHESIVE EPO 116 LOW MODULUS
MANF: COMMERCIAL CHEMICAL
....NO TEST DATA AVAILABLE....

66136 ADHESIVE EPO ALL-PURPOSE
MANF: COMMERCIAL CHEMICAL
....NO TEST DATA AVAILABLE....

67169 ADHESIVE EPOC RESIN 0108
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

66848 ADHESIVE EPOCAP 13050
MANF: HARDMAN INC
....NO TEST DATA AVAILABLE....

66849 ADHESIVE EPOCAP 3195 WITH EPOCURE S-L
MANF: HARDMAN INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005241 1

05181 ADHESIVE EPOCAST 1310 MOD-I/9223 GID: ABBGXX

MANF: FURANE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.343		00.06	10.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.83	.02	.00	72H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

05297 ADHESIVE EPOCAST 212 EPOXY GID: ABBGXX

MANF: FURANE

....NO TEST DATA AVAILABLE....

06532 ADHESIVE EPOCAST 2201/C951 GID: ABBGXX

MANF: FURANE

....NO TEST DATA AVAILABLE....

06136 ADHESIVE EPOCAST 290 EPOXY GID: ABBGXX

MANF: FURANE

....NO TEST DATA AVAILABLE....

66665 ADHESIVE EPOCAST 290 T2

MANF: FURANE

....NO TEST DATA AVAILABLE....

61895 ADHESIVE EPOCAST 290/9810 GID: ABBGXX

MANF: FURANE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.017	0.003	00.26	12.00	T MOD
X	1	100.0	016.5	0.017	0.003	01.25	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-7	.98	.00		24H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00060.68	24H-70F-

66675 ADHESIVE EPOCAST 35

MANF: FURANE

....NO TEST DATA AVAILABLE....

66674 ADHESIVE EPOCAST 45

MANF: FURANE

....NO TEST DATA AVAILABLE....

66673 ADHESIVE EPOCAST 50-1

MANF: FURANE

....NO TEST DATA AVAILABLE....

66672 ADHESIVE EPOCAST 50-2

MANF: FURANE

....NO TEST DATA AVAILABLE....

66671 ADHESIVE EPOCAST 50-3

MANF: FURANE

....NO TEST DATA AVAILABLE....

05470 ADHESIVE EPOCAST 8542/38/9242 EPX GID: ABBGXX

MANF: FURANE SPEC: GA100BET

MSFC-HDBK-527 REV F 9999942 0005242 3

Information Handling Services, 2000

05470 ADHESIVE EPOCAST 8542/38/9242 EPX (cont)

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.010	0.010		01.60	NONE	No test data		No test data							

06348 ADHESIVE EPOCAST 87005 A/B-60 GID: ABBGXX
MANF: FURANE

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	020.9	014.7	0.308			00.10	NONE	No test data		No test data							
X	1	020.9	014.7	0.308			11.50	MOD										

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	6.51	2.89	.51	2.5H-124F-	No test data		

66670 ADHESIVE EPOCAST 88757
MANF: FURANE
....NO TEST DATA AVAILABLE....

85410 ADHESIVE EPOLITE 5313 EPOXY RESIN GID: ABXXXX
MANF: HEXCEL

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	024.5	014.5	0.032	0.003	00.08	12.00	T LARGE	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data							A 25.06	

67661 ADHESIVE EPON 1001F
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

60731 ADHESIVE EPON 1001F/VERSAMID 115 GID: ABXXXX
MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	12.03	.03	.00	1H-210F-	No test data		

67662 ADHESIVE EPON 1002F
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

67663 ADHESIVE EPON 1004F
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

67664 ADHESIVE EPON 1007F
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

67665 ADHESIVE EPON 1009F
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

67672 ADHESIVE EPON 1031
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005243 5

67674 ADHESIVE EPON 1031A-70
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

67673 ADHESIVE EPON 1031B-80
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

60181 ADHESIVE EPON 812 GID: ABXXXX
MANF: SHELL CHEMICAL SPEC: STW5-2820
....NO TEST DATA AVAILABLE....

67654 ADHESIVE EPON 813
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

67656 ADHESIVE EPON 8132
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

05780 ADHESIVE EPON 815 EPOXY GID: ABBGXX
MANF: SHELL CHEMICAL SPEC: MIL-R-9300 PR9-181-1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.3	0.065			12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.79	.00	.00	44H-151F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00020.59	

62449 ADHESIVE EPON 815 WITH EPOCAST HN951 GID: ABXXXX
MANF: M & T CHEMICALS
SHELL CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.005	0.003		05.80	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.83	.01	.00	2H-126F- 1H-127F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

61715 ADHESIVE EPON 815/CAT Z EPOXY GID: DPBGXX
MANF: SHELL CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.003	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.003	0.003		00.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00004.28	2H-175F- 2H-300F-

20551 ADHESIVE EPON 815/DTA GID: AKBGXX
MANF: SHELL CHEMICAL SPEC: SVHS 8091T7

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.030	0.003	00.00	00.00	NONE
A	1	100.0	020.2	0.030	0.003		00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005244 7

20551 ADHESIVE EPON 815/DTA (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.68	.41	.00	168H-70F-

ODOR

RT	RT WEIGHT	CURE
A	A 00020.01	

TOXICITY

20552 ADHESIVE EPON 815/DTA/PHENOLIC F GID: ABBGXX

MANF: SHELL CHEMICAL SPEC: SVHS 8091T6

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.142	0.003		01.10	NONE
X	1	100.0	020.2	0.142	0.003	01.09	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.46	.00		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.14	

TOXICITY

61682 ADHESIVE EPON 815/EPC190/AP5 GID: ABBGXX

MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	7.6E-6	.38	.00		16H-160F-
					4H-250F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61205 ADHESIVE EPON 815/EPC190/AP5V GID: ABBGXX

MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	7.9E-6	.34	.00		SEE TEST REPORT

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05779 ADHESIVE EPON 815/MDA EPOXY GID: AZBJXX

MANF: SHELL CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.006	0.010		00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.5E-6	.75	.01	.42	

ODOR

RT	RT WEIGHT	CURE
A	B 00021.53	4H-250F-
		168H-70F-

TOXICITY

05920 ADHESIVE EPON 815/RF61/GL FT102 GID: ABXXXX

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

82649 ADHESIVE EPON 815/V15

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

82650 ADHESIVE EPON 815/V25

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

20775 ADHESIVE EPON 820/CAT U EPOXY GID: ABBGXX

MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.98	.02	.26	168H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005245 9

61035 ADHESIVE EPON 8201/CAT Z/HMS FIBE GID: BBBVXX
MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	2.2E-6	.78	.17	.26	6H-225F- 2H-300F-	No test data		

57655 ADHESIVE EPON 823
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

60138 ADHESIVE EPON 825 GID: ABBGXX
MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.47	.00	.00		No test data		

61755 ADHESIVE EPON 825/EPICURE 855 GID: ABBGFW
MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.33	.00		24H-70F-	No test data		

61204 ADHESIVE EPON 825/HV GID: ABBGXX
MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	7.6E-6	.63	.00		12H-160F- 2H-250F-	No test data		

61202 ADHESIVE EPON 825/HV/MEK-V GID: ABBGXX
MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.10	.00	.00	SEE TEST REPORT	No test data		

82651 ADHESIVE EPON 826/1031/EMI24
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82652 ADHESIVE EPON 826/1031/HMA/EMI24
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82653 ADHESIVE EPON 826/1031/HMA/PYRADINE
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

61641 ADHESIVE EPON 826/BDE/T6040 GID: ABBGXX
MANF: CELANESE SPEC: HBRF55A
SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82654 ADHESIVE EPON 826/BF3MEA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005246 0

Information Handling Services, 2000

82655 ADHESIVE EPON 826/DADS/BF3MEA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82656 ADHESIVE EPON 826/DDS/BF3MEA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82657 ADHESIVE EPON 826/MHPA/BDMA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82658 ADHESIVE EPON 826/MPDA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82659 ADHESIVE EPON 826/MPDA/ANILINE
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82660 ADHESIVE EPON 826/MTHPA/BDMA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82661 ADHESIVE EPON 826/NMA/EMI24
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82662 ADHESIVE EPON 826/PAPA/BDMA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82663 ADHESIVE EPON 826/Y
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

65094 ADHESIVE EPON 826/Z GID: ABBGXX
MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.04	

62721 ADHESIVE EPON 828 EPOXY GID: ABBGXX
MANF: SHELL CHEMICAL
SPEC: MIL-R-9300

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.3	0.040		00.02	04.00	T NONE
X	1	030.0	010.0	0.010	0.003	00.90	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.66	.01	.00	72H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00024.34	

82664 ADHESIVE EPON 828/1031/EMI24
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005247 2

82665 ADHESIVE EPON 828/1031/MTHPA/EMI24
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82666 ADHESIVE EPON 828/1031/Y
MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.25	.02	.00	1H-149F- 1H-180F- 4H-351F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

82667 ADHESIVE EPON 828/871/AEP
MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.38	.03	.00	12H-70F- 16H-149F- 400H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

82669 ADHESIVE EPON 828/871/MDA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82670 ADHESIVE EPON 828/871/NMA/EMI24
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82672 ADHESIVE EPON 828/871/Z
MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.64	.01	.00	2H-176F- 1H-266F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

82673 ADHESIVE EPON 828/872/AEP
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82675 ADHESIVE EPON 828/872/Z
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82676 ADHESIVE EPON 828/AEP
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82677 ADHESIVE EPON 828/BF3MEA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

06281 ADHESIVE EPON 828/C906 GID: ABXXXX
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82678 ADHESIVE EPON 828/CA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005248 4

20222 ADHESIVE EPON 828/CAT U EPOXY GID: ABBCXX

MANF: SHELL CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.009	0.003	00.00	00.00	NONE
X	1	025.9	014.3	0.009	0.003	00.68	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.48	.00	.00	2H-351F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.96	168H-70F-

82679 ADHESIVE EPON 828/D

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

82680 ADHESIVE EPON 828/D230

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

82681 ADHESIVE EPON 828/D230/AEP

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

82682 ADHESIVE EPON 828/D400

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

82683 ADHESIVE EPON 828/DADS

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

82684 ADHESIVE EPON 828/DADS/BF3MEA

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

82685 ADHESIVE EPON 828/DDSA/EMI24

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

82686 ADHESIVE EPON 828/DETA

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

82687 ADHESIVE EPON 828/DSA/BDMA

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

65162 ADHESIVE EPON 828/DTA 7500 GLASS GID: ABFVXX

MANF: MARTIN MARIETTA
SHELL CHEMICAL

SPEC: MMC STP 70021

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	015.0	0.072		00.06	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00203.70	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005249 6

00065 ADHESIVE EPON 828/DTA EPOXY GID: ABBGXX

MANF: SHELL CHEMICAL

SPEC: ABO130-010 C3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	030.0	010.0	0.006	0.003	00.00	00.00	NONE
B	1	030.0	010.0	0.006	0.003	00.20	09.00	SMALL
B	2	030.0	010.0	0.003	0.003	00.00	00.00	NONE
B	1	030.0	010.0	0.003	0.003	00.30	07.70	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.42	.01	.00	168H-70F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00021.08	24H-70F- 24H-150F-

06591 ADHESIVE EPON 828/DTA EPOXY GL FL GID: ABBGXX

MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.77	.03	.00	168H-70F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

20480 ADHESIVE EPON 828/EM308 EPOXY GID: ABBGXX

MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.30	.01	.00	1.5H-149F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

82688 ADHESIVE EPON 828/EMI24

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

82689 ADHESIVE EPON 828/EMPOL1040/DMP10

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

62450 ADHESIVE EPON 828/EPOCAST HN951 GID: ABXXXX

MANF: FURANE
M & T CHEMICALS
SHELL CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.005	0.003		03.70	MOD
I	1	020.9	014.7	0.010	0.003	00.40	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.010	00	20
X	MECH	14.7	10	-297	0.020	01	09
X	MECH	50	10	-297	0.020	01	13
C	MECH	50	60	70	0.010	00	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	2.7E-6	.76	.00	.55	.5H-70F- 2H-212F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

82690 ADHESIVE EPON 828/HHPA/BDMA

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

82691 ADHESIVE EPON 828/HHPA/DMP30

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005250 2

82692 ADHESIVE EPON 828/MHPA/EMI24
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82693 ADHESIVE EPON 828/IPD
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82694 ADHESIVE EPON 828/L ARAMINE C260
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82695 ADHESIVE EPON 828/LP3/DMP30
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE:...

82696 ADHESIVE EPON 828/MDA
MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.90	.10	.00	4H-351F-	No test data		

82697 ADHESIVE EPON 828/MDA/DMP30
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82698 ADHESIVE EPON 828/MPDA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82699 ADHESIVE EPON 828/MPDA/SILICA FILLER
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82700 ADHESIVE EPON 828/MTHPA/BDMA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82701 ADHESIVE EPON 828/NMA/BDMA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82703 ADHESIVE EPON 828/PA/BDMA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82704 ADHESIVE EPON 828/PACM20
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82705 ADHESIVE EPON 828/PAPA/BDMA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82706 ADHESIVE EPON 828/PAPA/EMI24
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005251 4

82707 ADHESIVE EPON 828/PMDA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

05453 ADHESIVE EPON 828/RP7A EPOXY GID: ABBGXX
MANF: SHELL CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.100		00.11	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.2E-6	.58	.01		

ODOR

RT	RT WEIGHT
No test data	

TOXICITY

CURE

82708 ADHESIVE EPON 828/T1
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82709 ADHESIVE EPON 828/TETA
MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.68	.04	.00	72H-70F-

ODOR

RT	RT WEIGHT
No test data	

TOXICITY

CURE

82710 ADHESIVE EPON 828/THPA/BDMA
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82711 ADHESIVE EPON 828/THPA/EMI24
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82712 ADHESIVE EPON 828/V40
MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.32	.21	.00	

ODOR

RT	RT WEIGHT
No test data	

TOXICITY

CURE

06410 ADHESIVE EPON 828/VERSAMID 120 GID: ABXXXX
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

05787 ADHESIVE EPON 828/VERSAMID 125 GID: ABBHBG
MANF: COAST PROSEAL
GENERAL MILLS
SHELL CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	.003	0.11		03.02	MOD
B	2	025.9	014.3	0.007	0.003	00.00	00.00	NONE
B	1	025.9	014.3	0.007	0.003	00.10	10.10	NONE
B	2	030.0	010.0	0.007	0.003	00.00	00.00	NONE
B	1	030.0	010.0	0.007	0.003	00.10	08.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.2E-3	.44	.02		168H-70F-
					24H-150F-

ODOR

RT	RT WEIGHT
A	B 00022.05

TOXICITY

CURE
168H-70F-
2H-302F-

MSFC-HDBK-527 REV F 9999942 0005252 6

Information Handling Services, 2000

06190 ADHESIVE EPON 828/VERSAMID 140 GID: ABBGXX

MANF: COAST PROSEAL
SHELL CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
X	1	025.9	014.3	0.057		00.28	12.00	T	MOD
X	1	025.9	014.3	0.104		00.20	12.00	T	MOD
X	2	025.9	014.3	0.010	0.003	00.00	00.00		NONE
X	1	025.9	014.3	0.010	0.003	00.30	10.80		MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.81	.03	.00	12H-122F- 24H-257F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	24.74	

69797 ADHESIVE EPON 828/VERSAMID 828/VERSAMID 125

MANF: COAST PROSEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.009	0.006		03.62	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	34.40	

82713 ADHESIVE EPON 828/Y

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

05890 ADHESIVE EPON 828/Z CURING AGENT GID: ABXXXX

MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.64	.00	.00	168H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

82714 ADHESIVE EPON 828/ZZLA0822

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

67660 ADHESIVE EPON 8280

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

67657 ADHESIVE EPON 829

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

67658 ADHESIVE EPON 8294

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

67659 ADHESIVE EPON 830

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

67666 ADHESIVE EPON 834

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005253 8

82715 ADHESIVE EPON 834/HMA/DMP30
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82716 ADHESIVE EPON 834/THPA/DMP30
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

67667 ADHESIVE EPON 836
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

67668 ADHESIVE EPON 841
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

67669 ADHESIVE EPON 871
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82671 ADHESIVE EPON 871/PAPA/EMI24
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

67670 ADHESIVE EPON 872
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82717 ADHESIVE EPON 872/828/HHPA/DMP30
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82718 ADHESIVE EPON 872/828/V40
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82719 ADHESIVE EPON 872/871/AEP
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82720 ADHESIVE EPON 872/871/AEP/OCTYL AMINE
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

67671 ADHESIVE EPON 872X75
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

67675 ADHESIVE EPON DPS164
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

82668 ADHESIVE EPON/871/DDSA/EMI24
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005254 T

Information Handling Services, 2000

82702 ADHESIVE EPON/NMA/EMI-24
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

66469 ADHESIVE EPOTEK
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

06554 ADHESIVE EPOTEK 301 EPOXY GID: AEBJXX
MANF: EPOXY TECHNOLOGY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		02.30	NONE
X	2	025.9	014.3	0.158		00.05	12.00	T MOD
X	1	025.9	014.3	0.158		00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.30	.02	.00	24H-70F- 6H-149F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.77	24H-150F-

66470 ADHESIVE EPOTEK 301-2
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	2.62	1.03	.00	24H-70F-

ODOR
No test data

TOXICITY
No test data

66471 ADHESIVE EPOTEK 302
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

66472 ADHESIVE EPOTEK 310
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

61145 ADHESIVE EPOTEK 320 GID: AEBJXX
MANF: EPOXY TECHNOLOGY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		04.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.67	.24	.00	1H-158F- 1H-176F-

ODOR
No test data

TOXICITY

RT	WEIGHT	CURE

66473 ADHESIVE EPOTEK 330
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	10.42	.07	.00	24H-70F-

ODOR
No test data

TOXICITY

RT	WEIGHT	CURE

66474 ADHESIVE EPOTEK 331
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

60340 ADHESIVE EPOTEK 353 EPOXY GID: ABBGXX
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005255 1

66475 ADHESIVE EPOTEK 353ND
MANF: EPOXY TECHNOLOGY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.010	0.003	0.10	12.00	T LARGE
X	1	025.9	014.3	0.010	0.003	0.09	12.00	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	20.30	.02	.00	24H-70F- 5H-140F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	23.9	

66476 ADHESIVE EPOTEK 360
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

66477 ADHESIVE EPOTEK 360ST
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

66478 ADHESIVE EPOTEK 360T
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

66479 ADHESIVE EPOTEK 390
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

66480 ADHESIVE EPOTEK 394
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

66481 ADHESIVE EPOTEK 410E
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

69612 ADHESIVE EPOTEK 415G
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.85	.27	.00	24H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

66494 ADHESIVE EPOTEK 444
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

66495 ADHESIVE EPOTEK 454
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

60992 ADHESIVE EPOTEK 877
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

66482 ADHESIVE EPOTEK 905
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005256 3

66483 ADHESIVE EPOTEK H205
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

66484 ADHESIVE EPOTEK H20E175
MANF: EPOXY TECHNOLOGY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.012		00.15	12.00	Y NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.18	.01	.00	2H-212F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66485 ADHESIVE EPOTEK H20S
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.54	.01	.00	2H-212F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66486 ADHESIVE EPOTEK H21D
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.20	.00	.00	.5H-212F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66487 ADHESIVE EPOTEK H22
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	1.00	.01	.00	3.5H-122F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66488 ADHESIVE EPOTEK H27D
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.52	.09	.00	1H-302F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66489 ADHESIVE EPOTEK H31
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.70	.00	.39	4H-302F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66490 ADHESIVE EPOTEK H31D
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.53	.00	.17	4H-257F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61195 ADHESIVE EPOTEK H31LV GID: AEBGXX
MANF: EPOXY TECHNOLOGY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.47	.02	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005257 5

66491 ADHESIVE EPOTEK H40
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.19	.00	.00	1H-248F-	No test data		

66492 ADHESIVE EPOTEK H41
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.15	.00	.00	1H-302F-	No test data		

66493 ADHESIVE EPOTEK H43
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.05	.01		1H-248F-	No test data		

66496 ADHESIVE EPOTEK H55
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.04	.00	.00	1H-212F-	No test data		

61135 ADHESIVE EPOTEK H61 GID: ABBGXX
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	4.31	.59	4.19	4H-300F-	No test data		

66497 ADHESIVE EPOTEK H62
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.45	.00	.21	4H-302F-	No test data		

06356 ADHESIVE EPOTEK H70E EPOXY GID: ABXXXX
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.99	.03	.00	12H-140F- 432H-77F-	No test data		

66498 ADHESIVE EPOTEK H70E4
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

66499 ADHESIVE EPOTEK H70S
MANF: EPOXY TECHNOLOGY
....NO TEST DATA AVAILABLE....

05220 ADHESIVE EPOTEK H72 EPOXY GID: DPBGXX
MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.31	.00	.00	.5H-212F-	No test data		

MSFC-HDBK-527 REV F 9999942 0005258 7

Information Handling Services, 2000

66500 ADHESIVE EPOTEK H74

MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.56	.01	.00	.5H-302F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

61625 ADHESIVE EPOTEK H77 GID: ABBGXX

MANF: EPOXY TECHNOLOGY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.015			00.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00056.70	.5H-302F-

66501 ADHESIVE EPOTEK H81

MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.06	.02	.00	12H-122F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

66502 ADHESIVE EPOTEK H81E

MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.20	.01	.00	2H-212F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

66503 ADHESIVE EPOTEK P10

MANF: EPOXY TECHNOLOGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.68	.03	2.13	4H-302F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

66504 ADHESIVE EPOTEK P1011

MANF: EPOXY TECHNOLOGY

....NO TEST DATA AVAILABLE....

66850 ADHESIVE EPOWELD 13230

MANF: HARDMAN INC

....NO TEST DATA AVAILABLE....

66852 ADHESIVE EPOWELD 2156 WITH EPOCURE 110

MANF: HARDMAN INC

....NO TEST DATA AVAILABLE....

66853 ADHESIVE EPOWELD 2156 WITH EPOCURE 118

MANF: HARDMAN INC

....NO TEST DATA AVAILABLE....

66851 ADHESIVE EPOWELD 2156 WITH EPOCURE S9

MANF: HARDMAN INC

....NO TEST DATA AVAILABLE....

66854 ADHESIVE EPOWELD 3243 HIGH IMPACT STRENGTH ADHESIVE

MANF: HARDMAN INC

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005259 9

66855 ADHESIVE EPOWELD 3583 WITH EPOCURE S-L HIGH IMPACT STRENGTH ADHESIVE
MANF: HARDMAN INC
....NO TEST DATA AVAILABLE....

66856 ADHESIVE EPOWELD 3650 PASTE FORM HIGH STRENGTH ADHESIVE
MANF: HARDMAN INC
....NO TEST DATA AVAILABLE....

66857 ADHESIVE EPOWELD 7781
MANF: HARDMAN INC
....NO TEST DATA AVAILABLE....

66858 ADHESIVE EPOWELD 7895 HIGH STRENGTH GENERAL PURPOSE ADHESIVE
MANF: HARDMAN INC
....NO TEST DATA AVAILABLE....

66859 ADHESIVE EPOWELD 7903
MANF: HARDMAN INC
....NO TEST DATA AVAILABLE....

66860 ADHESIVE EPOWELD 7982
MANF: HARDMAN INC
....NO TEST DATA AVAILABLE....

60341 ADHESIVE EPOWELD 8173 GID: ABXXXX
MANF: HARDMAN INC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.15	.04	.32	24H-70F-	No test data		

66861 ADHESIVE EPOWELD 8185
MANF: HARDMAN INC
....NO TEST DATA AVAILABLE....

66862 ADHESIVE EPOWELD 8200 HIGH IMPACT STRENGTH AD IMPACT STRENGTH ADHESIVE
MANF: HARDMAN INC
....NO TEST DATA AVAILABLE....

66863 ADHESIVE EPOWELD 8269 20 MINUTE SETTING ADHESIVE
MANF: HARDMAN INC
....NO TEST DATA AVAILABLE....

66864 ADHESIVE EPOWELD 9143A THIXOTROPIC FLEXIBLE ADHESIVE
MANF: HARDMAN INC
....NO TEST DATA AVAILABLE....

20144 ADHESIVE EPOXY GID: ABBGXX
MANF: SPEC: MIL-A-46864
....NO TEST DATA AVAILABLE....

67400 ADHESIVE EPOXY 10
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

62557 ADHESIVE EPOXY 11 GID: ABBGXX
MANF: TRANSENE

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
I	1.0E-6	.60	.09	.54	5H-300F-	No test data		

MSFC-HDBK-527 REV F 9999942 0005260 5

Information Handling Services, 2000

67401 ADHESIVE EPOXY 12
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67402 ADHESIVE EPOXY 13
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67403 ADHESIVE EPOXY 14
MANF: TRANSENE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.60	.31	.00	.5H-239F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

67404 ADHESIVE EPOXY 15
MANF: TRANSENE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.34	.21	.00	.33H-284F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

67405 ADHESIVE EPOXY 16
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67406 ADHESIVE EPOXY 17
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67407 ADHESIVE EPOXY 20
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67408 ADHESIVE EPOXY 30
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67409 ADHESIVE EPOXY 50
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

05942 ADHESIVE EPOXY 500 GID: ABBGXX
MANF: BLH ELECTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005	0.003		02.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61161 ADHESIVE EPOXY 77 GID: ABBGXX
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.4E-6	10.71	5.11		24H-70F- 24H-150F-

ODOR

RT
X

TOXICITY

RT	RT WEIGHT	CURE
X	00002.55	24H-70F- 24H-150F-

67410 ADHESIVE EPOXY 850
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005261 7

06526 ADHESIVE EPOXY 9-7844 B STAGE GID: ABBGXX
MANF: BENDIX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.006	0.003		00.60	NONE
A	1	025.9	014.7	0.006	0.003		00.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00000.90	SEE TEST DOCUMENT

60414 ADHESIVE EPOXY 907 GID: ABBGXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.25	.66	.00	168H-70F- 24H-113F- 8H-140F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

20538 ADHESIVE EPOXY 94318 GID: ABBGXX
....NO TEST DATA AVAILABLE....

05845 ADHESIVE EPOXY A01503 GID: ABBGXX
....NO TEST DATA AVAILABLE....

20183 ADHESIVE EPOXY B101 GID: ABBGXX
MANF: WESTINGHOUSE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.005	0.003		04.50	SMALL
A	1	033.0	014.3	0.003	0.003		05.90	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-7	.29	.00		1H-70F- 24H-70F- 4H-392F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00011.32	SEE TVS CURE1

67411 ADHESIVE EPOXY BOND ADHESIVE
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

06482 ADHESIVE EPOXY CDS64 GID: ABBGXX
....NO TEST DATA AVAILABLE....

20695 ADHESIVE EPOXY DGBA
MANF: BOURNS INC
....NO TEST DATA AVAILABLE....

61927 ADHESIVE EPOXY EPY150 GID: ABBGXX
MANF: BLH ELECTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.003		05.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-7	.73	.00		72H-70F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

61929 ADHESIVE EPOXY ER825A GID: ABBGXX
MANF: HAVEG SPEC: MMM-A-134T1

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005262 9

61929 ADHESIVE EPOXY ER825A (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.008	0.003	00.00	00.00	NONE
C	1	020.9	014.7	0.008	0.003	00.53	12.00	T SMALL
C	2	025.9	014.3	0.008	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.008	0.003	00.66	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.84	.01	.00	48H-167F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

62232 ADHESIVE EPOXY EXTRA FAST SETTING GID: ABBGX

MANF: COLE PARMER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.79	.01	.00	24H-70F-
					2H-212F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

62407 ADHESIVE EPOXY FA8/BA5 GID: ABBGXX

MANF: BACON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	022.0	0.002	0.003	00.40	12.00	T MOD
X	1	100.0	022.0	0.002	0.003	03.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.3E-6	.37	.04	.33	2H-200F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00019.45	2H-200F-

TOXICITY

62240 ADHESIVE EPOXY FM300M GID: ABBGXX

MANF: AMERICAN CYANAMID

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.06	.01		2H-351F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

85439 ADHESIVE EPOXY FM73 POLYESTER FILM

MANF: AMERICAN CYANAMID

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.004	0.125		00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

60357 ADHESIVE EPOXY FM73M FILM ON POLYESTER MAT GID: ABBGXX

SPEC: LAC30-4666

MANF: AMERICAN CYANAMID

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.008	0.003	00.09	03.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.97	.15	.00	1.5H-250F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60116 ADHESIVE EPOXY LCA9/BA5 GID: ABBGXX

MANF: BACON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.23	.03	.00	2H-199F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

06444 ADHESIVE EPOXY M688 GID: ABBGXX

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005263 0

05605 ADHESIVE EPOXY P460 GID: ABBGXX

MANF: APPLIED PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.022	0.003	00.00	00.00	NONE
X	1	023.8	014.5	0.022	0.003	00.50	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.18	.17	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00049.35	24H-70F- 24H-150F-

05074 ADHESIVE EPOXY PASTE CORFIL 6/5 GID: ABBGXX

MANF: AMERICAN CYANAMID

....NO TEST DATA AVAILABLE....

61134 ADHESIVE EPOXY PATCH KIT GID: ABBGXX

MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.027	0.100		01.90	SMALL
A	1	030.0	009.0	0.020	0.100		00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.27	.01	.00	24H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00020.06	168H-70F- 24H-150F-

20455 ADHESIVE EPOXY PATCH KIT 0151 CLEAR A/B GID: ABBGXX

MANF: HYSOL/DEXTER SPEC: V0707&V0630

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.009	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.009	0.003	00.57	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.57	.00	.00	2H-149F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.36	2H-140F-

66338 ADHESIVE EPOXY PATCH KIT 1105

MANF: HYSOL/DEXTER

....NO TEST DATA AVAILABLE....

06129 ADHESIVE EPOXY PATCH KIT 1C GID: ABBGXX

MANF: HYSOL/DEXTER SPEC: DP4024 DP85193

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.018		00.00	00.00	NONE
X	1	025.9	014.3	0.018		00.30	12.00	T MOD
		100.0	020.2					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.82	.40	.00	24H-70F- 24H-150F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00020.33	24H-70F- 24H-150F-

66339 ADHESIVE EPOXY PATCH KIT 309

MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.54	.81	.00	.07H-46F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005264 2

66340 ADHESIVE EPOXY PATCH KIT 3X

MANF: HYSOL/DEXTER

....NO TEST DATA AVAILABLE....

06171 ADHESIVE EPOXY PATCH KIT 56C WHITE GID: ABBGXX

MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.010	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.010	0.003	00.60	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.34	.02	.00	6H-77F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.44	24H-70F-
		24H-150F-

06170 ADHESIVE EPOXY PATCH KIT 608 GID: ABBGXX

MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.050			12.00	T MOD
A	1	023.8	014.5	0.007	0.003		05.50	SMALL
C	2	025.9	014.3	0.011	0.003	00.00	00.00	T NONE
C	1	025.9	014.3	0.011	0.003	00.40	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.93	.01	.00	.05H-140F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00015.90	24H-70F-
		24H-150F-

66341 ADHESIVE EPOXY PATCH KIT 615

MANF: HYSOL/DEXTER

....NO TEST DATA AVAILABLE....

66342 ADHESIVE EPOXY PATCH KIT 6C

MANF: HYSOL/DEXTER

....NO TEST DATA AVAILABLE....

62273 ADHESIVE EPOXY PATCH KIT 907 GREEN GID: ABBGXX

MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.031	0.010	00.00	00.00	NONE
C	1	025.9	014.3	0.031	0.010	00.14	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00021.61	168H-70F-
		24H-150F-

06231 ADHESIVE EPOXY PATCH KIT 9340 GID: ABBGXX

MANF: HYSOL/DEXTER SPEC: MIL-MMM-A-132

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.006	0.003		03.10	SMALL
B	1	033.0	014.3	0.005	0.003	00.19	07.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	1.61	.02	.00	2H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00018.71	2H-70F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005265 4

62221 ADHESIVE EPOXY PUTTY A/B GID: ABBGXX

MANF: BIGGS CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	6.0E-6	.48	.05		168H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

60672 ADHESIVE EPOXY R313 GID: ABBGXX

MANF: BEI ELECTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.250	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.71	.19	.00	12H-70F- 2H-151F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

06180 ADHESIVE EPOXY R82038/HD3475 GID: ABBGXX

MANF: HYSOL/DEXTER SPEC: T0601/T0930

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.011	0.003	00.04	12.00	T MOD
X	1	025.9	014.3	0.011	0.003	00.37	12.00	T MOD
C	2	025.9	014.3	0.006	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.006	0.003	00.37	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.53	.00		24H-70F- 24H-150F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00023.09	24H-70F- 24H-150F-

80184 ADHESIVE EPOXY RESIN RE103 GID: ABXXXX

MANF: DAINIPPON INK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	.024.5	014.5	0.030			00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	A 26.964	

60289 ADHESIVE EPOXY RTC GID: ABBGXX

MANF: W T BEAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.016	0.003	00.00	00.00	NONE
A	1	020.9	014.7	0.016	0.003		03.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.57	.07		24H-70F- 1H-115F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

06049 ADHESIVE EPOXY RW1290-82 GID: ABBGXX

....NO TEST DATA AVAILABLE....

20823 ADHESIVE EPOXY SILVER FILLED K20 GID: ABBGGQ

MANF: HYSOL/DEXTER SPEC: MB0120-096T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.010	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005266 6

20823 ADHESIVE EPOXY SILVER FILLED K20 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.010	0.003		06.00	SMALL

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.5E-6	3.88	.14	.12	SEE TEST REPORT

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62339 ADHESIVE EPOXY T1401 GID: ABBGXX

MANF: SHELDAHL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.97	.34	1.41	.5H-338F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61000 ADHESIVE EPOXY V5N734R24 GID: BDBGXX

MANF: SKINNER VALVE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.528			00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

05019 ADHESIVE EPOXY WS1183 CB5 GID: ABBGXX

MANF: B F GOODRICH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.5E-6	5.85	.01		24H-150F-

ODOR

RT	RT WEIGHT	CURE
X	00016.35	24H-150F-

TOXICITY

62157 ADHESIVE EPOXY XA924-40/E793 GID: ABBGXX

MANF: U S POLYMERIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.2E-5	1.00	.00		2H-350F- 24H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65892 ADHESIVE EPOXYBOND PUTTY

MANF: ATLAS CORP

....NO TEST DATA AVAILABLE....

66507 ADHESIVE EPOXYLITE 1462

MANF: EPOXYLITE CORP

....NO TEST DATA AVAILABLE....

69613 ADHESIVE EPOXYLITE 203

MANF: EPOXYLITE CORP

....NO TEST DATA AVAILABLE....

66505 ADHESIVE EPOXYLITE 211/C383

MANF: EPOXYLITE CORP

....NO TEST DATA AVAILABLE....

69614 ADHESIVE EPOXYLITE 221/C307

MANF: EPOXYLITE CORP

....NO TEST DATA AVAILABLE....

66508 ADHESIVE EPOXYLITE 223

MANF: EPOXYLITE CORP

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005267 8

66506 ADHESIVE EPOXYLITE 3101
MANF: EPOXYLITE CORP
....NO TEST DATA AVAILABLE....

66509 ADHESIVE EPOXYLITE 3351
MANF: EPOXYLITE CORP
....NO TEST DATA AVAILABLE....

66510 ADHESIVE EPOXYLITE 5302
MANF: EPOXYLITE CORP
....NO TEST DATA AVAILABLE....

06009 ADHESIVE EPOXYLITE 5403 EPOXY GID: ABBGXX
MANF: EPOXYLITE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.008	0.003	00.00	00.00	NONE
B	1	023.8	014.5	0.008	0.003		06.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.7E-6	.38	.01		8H-250F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00016.34	SEE TVS CURE1

66511 ADHESIVE EPOXYLITE 5526
MANF: EPOXYLITE CORP
....NO TEST DATA AVAILABLE....

60111 ADHESIVE EPOXYLITE 6001 COATING
MANF: EPOXYLITE CORP
....NO TEST DATA AVAILABLE....

05624 ADHESIVE EPOXYLITE 6203 COATING GID: ABXXXX
MANF: EPOXYLITE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.45	.03	.00	4H-250F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

05358 ADHESIVE EPOXYLITE 801-45 EPOXY GID: BABGXX
MANF: EPOXYLITE CORP
....NO TEST DATA AVAILABLE....

01173 ADHESIVE EPOXYLITE 801/C307 GID: ABXXXX
MANF: EPOXYLITE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.250		00.02	08.70	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.8E-6	.26	.00	.13	8H-250F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.07	

66512 ADHESIVE EPOXYLITE 810
MANF: EPOXYLITE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.19	.01	.14	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

67682 ADHESIVE EPOXYLITE 813
MANF: EPOXYLITE CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005268 T

05821 ADHESIVE EPOXYLITE 813-9 COATING GID: AKBGXX

MANF: EPOXYLITE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.007	0.003		04.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.0E-7	.43	.01		16H-200F- 1H-300F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

66513 ADHESIVE EPOXYLITE 8164

MANF: EPOXYLITE CORP

....NO TEST DATA AVAILABLE....

66514 ADHESIVE EPOXYLITE 8611

MANF: EPOXYLITE CORP

....NO TEST DATA AVAILABLE....

66515 ADHESIVE EPOXYLITE 8705

MANF: EPOXYLITE CORP

....NO TEST DATA AVAILABLE....

20453 ADHESIVE EPOXYLITE 8712 COATING GID: ALBGXX

MANF: EPOXYLITE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.007	0.003		01.40	NONE
C	1	025.9	014.3	0.007	0.003	00.93	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.42	.03	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00019.95	24H-70F- 24H-150F-

66516 ADHESIVE EPOXYLITE 8743

MANF: EPOXYLITE CORP

....NO TEST DATA AVAILABLE....

61001 ADHESIVE EPOXYLITE 8751 GID: ABBGXX

MANF: EPOXYLITE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.006	0.003		05.90	SMALL
A	1	030.0	009.0	0.005	0.003		04.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60183 ADHESIVE EPOXYLITE 8822 GID: ABXXXX

SPEC: STW5-2842

MANF: EPOXYLITE CORP

....NO TEST DATA AVAILABLE....

66517 ADHESIVE EPOXYLITE 8899

MANF: EPOXYLITE CORP

....NO TEST DATA AVAILABLE....

66518 ADHESIVE EPOXYLITE 8993

MANF: EPOXYLITE CORP

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005269 1

05359 ADHESIVE EPOXYLITE 9653 A/B EPOXY COATING GID: ABBGXX

MANF: EPOXYLITE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.001			03.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	21.71	.76	.00	1H-160F- 2H-160F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00002.61	24H-70F-

61894 ADHESIVE EPOXYLITE CF8628 COATING GID: AKBGXX

MANF: EPOXYLITE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.005	0.003		04.60	SMALL
B	1	033.0	014.3	0.005	0.003		06.50	NONE
X	1	100.0	016.5	0.005	0.003	01.19	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-7	.14	.00		2H-250F- 1H-350F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.03	2H-150F- 1H-350F-

06135 ADHESIVE EPOXYLITE CF8628 EP GID: ABBGXX

MANF: EPOXYLITE CORP

....NO TEST DATA AVAILABLE....

66536 ADHESIVE EUCO 352 GEL

MANF: EUCLID CHEMICAL

....NO TEST DATA AVAILABLE....

66537 ADHESIVE EUCO 352LV

MANF: EUCLID CHEMICAL

....NO TEST DATA AVAILABLE....

66538 ADHESIVE EUCO 352MV

MANF: EUCLID CHEMICAL

....NO TEST DATA AVAILABLE....

66539 ADHESIVE EUCO 452 GEL

MANF: EUCLID CHEMICAL

....NO TEST DATA AVAILABLE....

66540 ADHESIVE EUCO 452LV

MANF: EUCLID CHEMICAL

....NO TEST DATA AVAILABLE....

66541 ADHESIVE EUCO 452MV

MANF: EUCLID CHEMICAL

....NO TEST DATA AVAILABLE....

66532 ADHESIVE EUCO 456 MORTAR

MANF: EUCLID CHEMICAL

....NO TEST DATA AVAILABLE....

66542 ADHESIVE EUCO 456S

MANF: EUCLID CHEMICAL

....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005270 8

Information Handling Services, 2000

66543 ADHESIVE EUCO 460 GEL
MANF: EUCLID CHEMICAL
....NO TEST DATA AVAILABLE....

66544 ADHESIVE EUCO 460LV
MANF: EUCLID CHEMICAL
....NO TEST DATA AVAILABLE....

66545 ADHESIVE EUCO 460MV
MANF: EUCLID CHEMICAL
....NO TEST DATA AVAILABLE....

66549 ADHESIVE EUCO 520 GEL
MANF: EUCLID CHEMICAL
....NO TEST DATA AVAILABLE....

66551 ADHESIVE EUCO 520LV
MANF: EUCLID CHEMICAL
....NO TEST DATA AVAILABLE....

66550 ADHESIVE EUCO 520MV
MANF: EUCLID CHEMICAL
....NO TEST DATA AVAILABLE....

66533 ADHESIVE EUCO 620 GEL
MANF: EUCLID CHEMICAL
....NO TEST DATA AVAILABLE....

66534 ADHESIVE EUCO 620LV
MANF: EUCLID CHEMICAL
....NO TEST DATA AVAILABLE....

66535 ADHESIVE EUCO 620MV
MANF: EUCLID CHEMICAL
....NO TEST DATA AVAILABLE....

66546 ADHESIVE EUCO M235 C1
MANF: EUCLID CHEMICAL
....NO TEST DATA AVAILABLE....

66547 ADHESIVE EUCO M235 C2
MANF: EUCLID CHEMICAL
....NO TEST DATA AVAILABLE....

81489 ADHESIVE EUCO PLASTISEAL
MANF: EUCLID CHEMICAL
....NO TEST DATA AVAILABLE....

81490 ADHESIVE EUCO POLYSULFIDE SEALANT
MANF: EUCLID CHEMICAL
....NO TEST DATA AVAILABLE....

66548 ADHESIVE EUCOPOXY LT
MANF: EUCLID CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005271 T

Information Handling Services, 2000

66523 ADHESIVE F502
MANF: ETHERINGTON/U S PROLAM
....NO TEST DATA AVAILABLE....

65895 ADHESIVE FA1
MANF: BACON
....NO TEST DATA AVAILABLE....

67697 ADHESIVE FA13
MANF: BACON
....NO TEST DATA AVAILABLE....

65896 ADHESIVE FA14
MANF: BACON
....NO TEST DATA AVAILABLE....

65897 ADHESIVE FA21
MANF: BACON
....NO TEST DATA AVAILABLE....

65898 ADHESIVE FA8
MANF: BACON
....NO TEST DATA AVAILABLE....

66552 ADHESIVE FAIRPRENE V2-5159
MANF: DUPONT
....NO TEST DATA AVAILABLE....

67580 ADHESIVE FASTBOND 30 GREEN AND NEUTRAL
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67215 ADHESIVE FASTBOND 30NF GREEN
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67216 ADHESIVE FASTBOND 30NF NEUTRAL
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67219 ADHESIVE FASTBOND 35NF BLUE
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67226 ADHESIVE FASTBOND 38NF BLACK SELF-EXTINGUISHING
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67231 ADHESIVE FASTBOND 4213NF
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67232 ADHESIVE FASTBOND 4268NF
MANF: 3M CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005272 1 ■

67233 ADHESIVE FASTBOND 4289NF
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67229 ADHESIVE FASTBOND 42NF
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67230 ADHESIVE FASTBOND 42NF PLUS
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67234 ADHESIVE FASTBOND 45NF CLEAR
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67235 ADHESIVE FASTBOND 45NF ORANGE
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67237 ADHESIVE FASTBOND 47NF CLEAR
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67239 ADHESIVE FASTBOND 4910NF
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67251 ADHESIVE FASTBOND 871NF
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67566 ADHESIVE FASTBOND INSULATION ADHESIVE 33 RED
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67567 ADHESIVE FASTBOND INSULATION ADHESIVE 34 TRANSLUCENT
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67568 ADHESIVE FASTBOND INSULATION ADHESIVE 35NF BLUE
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67569 ADHESIVE FASTBOND INSULATION ADHESIVE 36 BLACK
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67570 ADHESIVE FASTBOND INSULATION ADHESIVE 37 BLACK
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67571 ADHESIVE FASTBOND INSULATION ADHESIVE 38NF BLACK
MANF: 3M CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005273 3 ■

Information Handling Services, 2000

81722 ADHESIVE FD4207
MANF: H B FULLER
....NO TEST DATA AVAILABLE....

20358 ADHESIVE FE7119 GID: ABXXXX
....NO TEST DATA AVAILABLE....

81103 ADHESIVE FELPRO GS1
MANF: FEL PRO INC
....NO TEST DATA AVAILABLE....

81107 ADHESIVE FELPRO GS2
MANF: FEL PRO INC
....NO TEST DATA AVAILABLE....

81110 ADHESIVE FELPRO GS3 SEALER
MANF: FEL PRO INC
....NO TEST DATA AVAILABLE....

81113 ADHESIVE FELPRO HPS SEALER
MANF: FEL PRO INC
....NO TEST DATA AVAILABLE....

81115 ADHESIVE FELPRO PROLOCK FLANGE SEALANT
MANF: FEL PRO INC
....NO TEST DATA AVAILABLE....

81116 ADHESIVE FELPRO PROLOCK PIPE SEALANT
MANF: FEL PRO INC
....NO TEST DATA AVAILABLE....

65899 ADHESIVE FFA2
MANF: BACON
....NO TEST DATA AVAILABLE....

65900 ADHESIVE FFA5
MANF: BACON
....NO TEST DATA AVAILABLE....

65901 ADHESIVE FFA9
MANF: BACON
....NO TEST DATA AVAILABLE....

66564 ADHESIVE FIBER RESIN 12/HARDENER 5
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66565 ADHESIVE FIBER RESIN 12/HARDENER 6
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66566 ADHESIVE FIBER RESIN 13
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66567 ADHESIVE FIBER RESIN 3118 A/B
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005274 5

Information Handling Services, 2000

66568 ADHESIVE FIBER RESIN 337 POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66569 ADHESIVE FIBER RESIN 5366 POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE:...

60079 ADHESIVE FIBER RESIN 55-9 GID: ABXXXX
....NO TEST DATA AVAILABLE....

81118 ADHESIVE FIBER RESIN 7010FR
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66570 ADHESIVE FIBER RESIN 7011 POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66556 ADHESIVE FIBER RESIN 7015-1 A/B
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66557 ADHESIVE FIBER RESIN 7016
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66558 ADHESIVE FIBER RESIN 7018 A/B
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66559 ADHESIVE FIBER RESIN 7026
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66571 ADHESIVE FIBER RESIN 7026 POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66560 ADHESIVE FIBER RESIN 7030
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66572 ADHESIVE FIBER RESIN 7031 POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66573 ADHESIVE FIBER RESIN 7035 POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66574 ADHESIVE FIBER RESIN 7037 POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66575 ADHESIVE FIBER RESIN 7106 POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005275 7

Information Handling Services, 2000

66576 ADHESIVE FIBER RESIN 7136-2 POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66577 ADHESIVE FIBER RESIN 7162 POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66578 ADHESIVE FIBER RESIN 7171 POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66579 ADHESIVE FIBER RESIN 7176 POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66561 ADHESIVE FIBER RESIN 7179
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66562 ADHESIVE FIBER RESIN 7182
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66580 ADHESIVE FIBER RESIN 7183 A/B POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66581 ADHESIVE FIBER RESIN 7332 POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66585 ADHESIVE FIBER RESIN 7336 POLYURETHANE
MANF: FIBER-RESIN CORP
..:.NO TEST DATA AVAILABLE....

66582 ADHESIVE FIBER RESIN 8193 A/B POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66583 ADHESIVE FIBER RESIN 8194 A/B POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66584 ADHESIVE FIBER RESIN 8503 POLYURETHANE
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66563 ADHESIVE FIBER RESIN 8516
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

60478 ADHESIVE FILM CMC122 GID: ACXXXX
MANF: OAK INDUSTRIES
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005276 9

Information Handling Services, 2000

00708 ADHESIVE FILM FM1000 POLYAMIDE GID: ACBLXX
MANF: AMERICAN CYANAMID SPEC: MMM-A-132

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.82	.15	.00	24H-250F-0psiaVACUUM

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

00509 ADHESIVE FILM FM123-2 FILM EPOXY GID: BPBGXX
MANF: AMERICAN CYANAMID

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	009.0	0.008	0.003	01.01	10.70 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.17	.02	.00	.5H-257F- 14H-302F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

06163 ADHESIVE FILM FM123-2LVC EPOXY GID: ABBGXX
MANF: AMERICAN CYANAMID SPEC: MIL-A-25463T1/2 MMM-A-132T1/2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.006	0.003	00.12	09.60	NONE
I	1	033.0	014.3	0.006	0.003	00.78	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.76	.00	.00	2H-250F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	X 00005.01	

64240 ADHESIVE FILM FM123-5
MANF: AMERICAN CYANAMID

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	V 91.90	

65691 ADHESIVE FILM FM150-2 LP15
MANF: AMERICAN CYANAMID

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.87	.07	.00	1H-351F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

65692 ADHESIVE FILM FM150-2U
MANF: AMERICAN CYANAMID

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.90	.03	.00	1H-351F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

06562 ADHESIVE FILM FM24 EPOXY GID: ACBGXX
MANF: AMERICAN CYANAMID SPEC: MB0120-078T5

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.31	.06	.00	2H-482F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

65697 ADHESIVE FILM FM30
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

62138 ADHESIVE FILM FM300 EPOXY GID: ACBGXX
MANF: AMERICAN CYANAMID SPEC: MIL-A-25463T2/2 MMM-A-132

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005277 0

69600 ADHESIVE FILM FM300K
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

65698 ADHESIVE FILM FM32
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

65684 ADHESIVE FILM FM33
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

65688 ADHESIVE FILM FM34B-18
MANF: AMERICAN CYANAMID

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.38	.00	.00	1.5H-351F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65689 ADHESIVE FILM FM34B-184
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

65696 ADHESIVE FILM FM36
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

65685 ADHESIVE FILM FM40
MANF: AMERICAN CYANAMID SPEC: AMS 3689

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.180	0.003	00.05	12.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.95	.00	.00	2H-338F- 16H-320F-

ODOR

RT	RT WEIGHT	CURE
A	59.0	

TOXICITY

64876 ADHESIVE FILM FM400 GID: ACBGXX
MANF: AMERICAN CYANAMID

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.015		00.65	11.50	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.13	.01	.00	6H-350F-

ODOR

RT	RT WEIGHT	CURE
A	V 16070.00	

TOXICITY

05127 ADHESIVE FILM FM400/BR400 WITH ALUMINUM GID: ACBGFK
MANF: AMERICAN CYANAMID

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.014	0.003	00.12	05.80	SMALL
A	1	030.0	009.0	0.016	0.003	00.96	05.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.2E-6	.46	.01		.17H-70F- 1H-225F- 1H-340F-

ODOR

RT	RT WEIGHT	CURE
A	B 00016.02	.17H-70F- 1H-225F- 1H-340F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005278 2

65686 ADHESIVE FILM FM404
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

65687 ADHESIVE FILM FM43
MANF: AMERICAN CYANAMID

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.28	.09	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

65694 ADHESIVE FILM FM96 STRUCTURAL
MANF: AMERICAN CYANAMID

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.94	.02	.94	1H-347F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

65695 ADHESIVE FILM FM96U STRUCTURAL
MANF: AMERICAN CYANAMID

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.15	.01	.00	1H-320F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

65690 ADHESIVE FILM FXM250
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

05877 ADHESIVE FILM LF0400 PYRALUX GID: ACAKXX
MANF: DUPONT SPEC: LF0400

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	1.38	.04	.40	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00016.72	

20777 ADHESIVE FLEXCRAFT 868 URETHANE/VINYL GID: ABXXXX
MANF: FLEXCRAFT IND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		02.30	NONE
A	1	030.0	009.0	0.001	0.003		02.10	NONE
C	1	100.0	020.2	0.001	0.003	01.76	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.8E-6	13.68	.00	.12	1H-70F-
					72H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00006.39	1H-70F-
		72H-70F-

65902 ADHESIVE FLEXOBOND 329
MANF: BACON
....NO TEST DATA AVAILABLE....

65903 ADHESIVE FLEXOBOND 423
MANF: BACON
....NO TEST DATA AVAILABLE....

65904 ADHESIVE FLEXOBOND 425
MANF: BACON
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005279 4

20797 ADHESIVE FLUOROCARB 6700 COPOLYMR GID: ABXXXX
....NO TEST DATA AVAILABLE....

80618 ADHESIVE FM137/BR127
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

0619 ADHESIVE FM238/BR238
MANF: AMERICAN CYANAMID

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	3.18	.64	.57	1H-351F-	No test data		

80620 ADHESIVE FM330
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

80622 ADHESIVE FM350/BR154
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

80623 ADHESIVE FM3505/BR154
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

80624 ADHESIVE FM53/BR53
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

80625 ADHESIVE FM53U/BR53
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

80626 ADHESIVE FM61/BR227
MANF: AMERICAN CYANAMID

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	.68	.21	.00	1H-347F-	No test data		

80627 ADHESIVE FM61/BR227A
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

80628 ADHESIVE FM73/BR127
MANF: AMERICAN CYANAMID

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.78	.00	.00	1H-248F-	No test data		
					1H-248F-			

80629 ADHESIVE FM73/BR73
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

80289 ADHESIVE FM73M ON GRAPHITE EPOXY PLATES T50/934 GID: ABXXXX
MANF: AMERICAN CYANAMID/LOCKHEED SPEC: LAC30-4666-0100

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
A	1	025.9	014.3	0.240		0.004	00.13	NONE	No test data		No test data							

MSFC-HDBK-527 REV F 9999942 0005280 0

Information Handling Services, 2000

80630 ADHESIVE FM73M/BR127
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

61446 ADHESIVE FOAM AF3018 EPOXY GID: CABGXX
MANF: 3M CO
SPEC: MB0120-077

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.091		00.02	12.00	T MOD
X	1	025.9	014.3	0.091		00.33	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.8E-6	1.25	.08	.85	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00019.96	

61447 ADHESIVE FOAM EA9814 EPOXY GID: CABGXX
MANF: HYSOL/DEXTER
SPEC: MB0120-077

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.085		00.02	12.00	T MOD
X	1	025.9	014.3	0.085		00.25	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.8E-6	.66	.01	.53	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00020.03	

05968 ADHESIVE FOAM FM37 MODIFIED EPOXY GID: ABBGXX
MANF: AMERICAN CYANAMID
SPEC: MB0120-080

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.100			03.50	NONE
X	1	025.9	014.3	0.100		00.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.25	.11	.00	1H-284F- 1H-284F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.00	

62139 ADHESIVE FOAM FM41 GID: ABBGXX
MANF: AMERICAN CYANAMID

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.88	.00	.28	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

05035 ADHESIVE FOAM HT424 T2 GID: ABBXXX
MANF: AMERICAN CYANAMID

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.18	.09	.00	30H-320F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

62538 ADHESIVE FOAM POLYURETHANE GID: CAXXXX
MANF: CALLERY CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	1.000		01.18	10.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.54	.16	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005281 2

81687 ADHESIVE FOMO 5-10
MANF: FLUOROCARBON CORP
....NO TEST DATA AVAILABLE....

66170 ADHESIVE FR1241/EA055
MANF: CONAP
....NO TEST DATA AVAILABLE....

81125 ADHESIVE FR14/NO.5 HARDENER
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

81127 ADHESIVE FR14/NO.6 HARDENER
MANF: FIBER-RESIN CORP
....NO TEST DATA AVAILABLE....

66728 ADHESIVE FS145
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66953 ADHESIVE FUSOR EPOXY ADHESIVES
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

80632 ADHESIVE FXM410
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

66705 ADHESIVE G10
MANF: GATES ENGINEERING CO INC
....NO TEST DATA AVAILABLE....

67193 ADHESIVE G404
MANF: STABOND CORP
....NO TEST DATA AVAILABLE....

81808 ADHESIVE G623
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81809 ADHESIVE G624
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81810 ADHESIVE G627
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81811 ADHESIVE G635
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81812 ADHESIVE G641
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.27	.14	.00	

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005282 4 ■

81813 ADHESIVE G662
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81814 ADHESIVE G687
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81815 ADHESIVE G697
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

66444 ADHESIVE G92
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66706 ADHESIVE GACO AL45
MANF: GATES ENGINEERING CO INC
....NO TEST DATA AVAILABLE....

66707 ADHESIVE GACO CE2
MANF: GATES ENGINEERING CO INC
....NO TEST DATA AVAILABLE....

81836 ADHESIVE GC1100
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

66750 ADHESIVE GC131 ADHESIVE PRIMER
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81837 ADHESIVE GC1500 CLASS A
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81838 ADHESIVE GC1500 CLASS B
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81839 ADHESIVE GC1900
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81840 ADHESIVE GC200 CLASS A
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81842 ADHESIVE GC200 CLASS B
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

66751 ADHESIVE GC3001
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005283 6

81844 ADHESIVE GC3007
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81845 ADHESIVE GC401 CLASS A
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81846 ADHESIVE GC401 CLASS B
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81847 ADHESIVE GC401LD CLASS A
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81848 ADHESIVE GC401LD CLASS B
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81849 ADHESIVE GC402
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81850 ADHESIVE GC407 CLASS A
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81851 ADHESIVE GC407 CLASS B
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81852 ADHESIVE GC408 CLASS A
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81853 ADHESIVE GC408 CLASS B
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81854 ADHESIVE GC409 CLASS B
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81855 ADHESIVE GC414 CLASS B2
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81856 ADHESIVE GC435
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81857 ADHESIVE GC450 CLASS A
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005284 8

Information Handling Services, 2000

81858 ADHESIVE GC450 CLASS B
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81859 ADHESIVE GC450 CLASS C
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81861 ADHESIVE GC502
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

66752 ADHESIVE GC531 MYLAR ADHESIVE (AEROSPACE)
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

66753 ADHESIVE GC656 ADHESIVE GAP FILLING
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

66754 ADHESIVE GC825 FLEXIBLE EPOXY ADHESIVE
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81862 ADHESIVE GC92
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

81860 ADHESIVE GCL455 CLASS B
MANF: GOAL CHEMICAL SEALANTS CORP
....NO TEST DATA AVAILABLE....

67412 ADHESIVE GE10
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67413 ADHESIVE GE20
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67414 ADHESIVE GE30
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67415 ADHESIVE GE40
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

20357 ADHESIVE GLYPTAL 7526F GID: ABXXXX
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

05354 ADHESIVE GOODRICH A1177 A/B EPOXY GID: ABBGXX
MANF: B F GOODRICH
SPEC: HP 16-25

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.009	0.003		02.40	NONE	No test data		No test data							

MSFC-HDBK-527 REV F 9999942 0005285 T

Information Handling Services, 2000

05354 ADHESIVE GOODRICH A1177 A/B EPOXY (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.005	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.005	0.003		03.10	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.45	.02	.00	24H-77F- .5H-180F-

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00066.92	1H-160F-

65806 ADHESIVE GRAPHIBOND 551A
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

65807 ADHESIVE GRAPHIBOND 551R
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

05964 ADHESIVE GRIGG G570 GID: ABBGXX
....NO TEST DATA AVAILABLE....

66463 ADHESIVE GRILTEX 1G
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

66464 ADHESIVE GRILTEX 2G
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

66465 ADHESIVE GRILTEX 4G
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

66466 ADHESIVE GRILTEX 5G
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

66467 ADHESIVE GRILTEX 6G
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

66468 ADHESIVE GRILTEX 8G
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

60157 ADHESIVE GRIP 10-115 GID: ABXXXX
....NO TEST DATA AVAILABLE....

81688 ADHESIVE HANDIFOAM
MANF: FLUOROCARBON CORP
....NO TEST DATA AVAILABLE....

81689 ADHESIVE HANDIFOAM 2
MANF: FLUOROCARBON CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005286 1

65523 ADHESIVE HE17017 E-Z KIT GID: ABXXXX
MANF: HARTEL ENTERPRISE

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	5.0E-6	2.65	.07	.50	168H-70F-	No test data		

80764 ADHESIVE HETRON 700
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

80765 ADHESIVE HETRON 800
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

61232 ADHESIVE HEXABOND 3 FILM GID: ABXXXX
MANF: HEXCEL

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.40	.30	.00	.25H-180F- 1H-250F-0psiaVACUUM	No test data		

67260 ADHESIVE HIGH STRENGTH ADHESIVE 90
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67679 ADHESIVE HIGH STRENGTH RTC EPOXY
MANF: WILLIAM T. BEAN MICRO ENGINEER
....NO TEST DATA AVAILABLE....

66843 ADHESIVE HM0904
MANF: H B FULLER
....NO TEST DATA AVAILABLE....

66844 ADHESIVE HM0964
MANF: H B FULLER
....NO TEST DATA AVAILABLE....

66847 ADHESIVE HM1357
MANF: H B FULLER
....NO TEST DATA AVAILABLE....

66846 ADHESIVE HM1752
MANF: H B FULLER
....NO TEST DATA AVAILABLE....

66845 ADHESIVE HM1756
MANF: H B FULLER
....NO TEST DATA AVAILABLE....

66708 ADHESIVE HP12
MANF: GATES ENGINEERING CO INC
....NO TEST DATA AVAILABLE....

00001 ADHESIVE HT424 EPOXY GID: ACBGBX
MANF: AMERICAN CYANAMID SPEC: MB0120-048

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.18	.09	.00	30H-320F-	A	B 00065.31	.67H-340F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005287 3

00507 ADHESIVE HT424 THIXOTROPIC PASTE GID: ABBXFK
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

20500 ADHESIVE HYLENE M50 GID: ABXXXX
MANF: DUPONT
SPEC: ST81M548-01/ILC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.002	0.003	00.00	00.00	NONE
B	1	025.9	014.3	0.002	0.003		06.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	6.2E-7	.61	.00		24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00012.34	24H-70F- 24H-150F-

05528 ADHESIVE HYSOL 4351/3469 GID: ABXXXX
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66979 ADHESIVE HYSOL EE4183
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

67680 ADHESIVE HYSOL EPOXY
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

67543 ADHESIVE HYSOL RE2039
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

60646 ADHESIVE IBM240 GID: ABBGXX
MANF: IBM CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.2E-6	4.70	.01	.19	.67H-240F- .67H-340F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

20210 ADHESIVE IBM314 EPOXY GID: ABBGXX
MANF: IBM CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	9.0E-7	2.70	.01		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00005.91	

84068 ADHESIVE IMPRUV 349
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

84069 ADHESIVE IMPRUV 365
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

84070 ADHESIVE IMPRUV 366
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005288 5

67544 ADHESIVE IMPRUV GENERAL PURPOSE ADHESIVE
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

67545 ADHESIVE IMPRUV SEALANT/ADHESIVE
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

66711 ADHESIVE IS802
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

66712 ADHESIVE IS803
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

66713 ADHESIVE IS808
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

20267 ADHESIVE ISOCHEM BOND 1308/95A6 GID: BABGXX
MANF: ISOCHEM RESINS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
B	2	025.9	014.3	0.007	0.003	00.00	00.00		NONE
B	1	025.9	014.3	0.007	0.003	00.10	08.00		SMALL
A	1	025.9	014.3	0.005	0.003	00.17	02.60		SMALL
X	1	030.0	010.0	0.007	0.003	00.40	12.00	T	MOD
B	2	030.0	010.0	0.005	0.003	00.00	00.00		NONE
B	1	030.0	010.0	0.005	0.003	00.19	07.20		SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.4E-6	2.12	.03	.30	24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00021.90	24H-70F-

67628 ADHESIVE ISOSET WD2A312
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

67629 ADHESIVE ISOSET WD3A320
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

60353 ADHESIVE ISOTAC ACRYLIC GID: ABAKXX
MANF: 3M CO
SPEC: LAC24-4693-0100
....NO TEST DATA AVAILABLE....

67261 ADHESIVE JET MELT 3735
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67263 ADHESIVE JET MELT 3736
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67264 ADHESIVE JET MELT 3738
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005289 7

67265 ADHESIVE JET MELT 3740
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67266 ADHESIVE JET MELT 3758
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67267 ADHESIVE JET MELT 3762
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67268 ADHESIVE JET MELT 3764
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67269 ADHESIVE JET MELT 3765
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67270 ADHESIVE JET MELT 3779
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67271 ADHESIVE JET MELT 3783
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67272 ADHESIVE JET MELT 3788
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67262 ADHESIVE JET MELT 3790
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67273 ADHESIVE JET MELT 3792
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67274 ADHESIVE JET MELT 3796
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67275 ADHESIVE JET MELT 3797
MANF: 3M CO
....NO TEST DATA AVAILABLE....

66918 ADHESIVE JOMAR SEAL "GIMME THE GREEN STUFF"
MANF: JOMAR INTERNATIONAL
....NO TEST DATA AVAILABLE....

66919 ADHESIVE JOMAR SEAL "THE HEAVYWEIGHT"
MANF: JOMAR INTERNATIONAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005290 3 ■

Information Handling Services, 2000

66920 ADHESIVE JOMAR SEAL "TUFFER THAN TUFF"
MANF: JOMAR INTERNATIONAL
....NO TEST DATA AVAILABLE....

66921 ADHESIVE JOMAR SEAL W.O.G. SEAL
MANF: JOMAR INTERNATIONAL
....NO TEST DATA AVAILABLE....

65905 ADHESIVE JR228-1
MANF: BACON
....NO TEST DATA AVAILABLE....

65906 ADHESIVE JR228A
MANF: BACON
....NO TEST DATA AVAILABLE....

05868 ADHESIVE JW7-12 ACRYLIC GID: ABXXXX
MANF: SPEC: MIL-T-50884
....NO TEST DATA AVAILABLE....

06488 ADHESIVE K230 B/A GID: ABBGXX
MANF: CONAP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.009	0.003	00.00	00.00	NONE
X	1	025.9	014.3	0.009	0.003		08.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00019.79	24H-70F-

66349 ADHESIVE KE4238
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66350 ADHESIVE KE4239
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66347 ADHESIVE KO1002
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66348 ADHESIVE KO109
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66351 ADHESIVE KO308
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66352 ADHESIVE KO309
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66355 ADHESIVE KS0001
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005291 5

66356 ADHESIVE KS0002
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66357 ADHESIVE KS0003
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66354 ADHESIVE KS14
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66358 ADHESIVE KS4007
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66359 ADHESIVE KS4008
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66128 ADHESIVE KWIKSTIK 1676 N/F
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66130 ADHESIVE KWIKSTIK 516
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66129 ADHESIVE KWIKSTIK 747
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

66923 ADHESIVE L & M CERAMIC FLOOR ADHESIVE 16
MANF: L & M-SURCO MFG, INC
....NO TEST DATA AVAILABLE....

67693 ADHESIVE L & M CERAMIC FLOOR ADHESIVE B272
MANF: L & M-SURCO MFG, INC
....NO TEST DATA AVAILABLE....

67694 ADHESIVE L & M CERAMIC WALL TILE ADHESIVE A282
MANF: L & M-SURCO MFG, INC
....NO TEST DATA AVAILABLE....

67695 ADHESIVE L & M MULTI-PURPOSE CERAMIC WALL AND TILE ADH TYPE 1 B-289
MANF: L & M-SURCO MFG, INC
....NO TEST DATA AVAILABLE....

81255 ADHESIVE L-M CERAMIC FLOOR
MANF: L & M-SURCO MFG, INC
....NO TEST DATA AVAILABLE....

67276 ADHESIVE LABELING ADHESIVE EC4944
MANF: 3M CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005292 7

Information Handling Services, 2000

66616 ADHESIVE LAMINATING 25
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66617 ADHESIVE LAMINATING GLUE 6W
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

65908 ADHESIVE LCA127
MANF: BACON
....NO TEST DATA AVAILABLE....

65909 ADHESIVE LCA12XM
MANF: BACON
....NO TEST DATA AVAILABLE....

65910 ADHESIVE LCA14
MANF: BACON
....NO TEST DATA AVAILABLE....

65911 ADHESIVE LCA20
MANF: BACON
....NO TEST DATA AVAILABLE....

65912 ADHESIVE LCA21
MANF: BACON
....NO TEST DATA AVAILABLE....

65913 ADHESIVE LCA24
MANF: BACON
....NO TEST DATA AVAILABLE....

65914 ADHESIVE LCA4
MANF: BACON
....NO TEST DATA AVAILABLE....

20049 ADHESIVE LCA4/BA5 EPOXY GID: ABBGXX
MANF: BACON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	012.3	0.015	0.003		01.10	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
	No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.20	.00	.00	16H-212F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00126.35	2H-200F-

65915 ADHESIVE LCA4LV
MANF: BACON
....NO TEST DATA AVAILABLE....

65916 ADHESIVE LCA9
MANF: BACON
....NO TEST DATA AVAILABLE....

06175 ADHESIVE LEFKOWELD 109/LM52 EPOXY GID: ABBGXX
MANF: LEFFINGWELL CHEM CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.011	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
	No test data						

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005293 9

06175 ADHESIVE LEFKOWELD 109/LM52 EPOXY (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	020.9	014.7	0.011	0.003	00.60	12.00 T	SMALL
B	2	023.8	014.5	0.008	0.003	00.00	00.00	NONE
B	1	023.8	014.5	0.008	0.003		07.50	NONE
B	2	025.9	014.3	0.010	0.003	00.00	00.00	NONE
B	1	025.9	014.3	0.010	0.003		08.70	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.85	.03	.00	24H-70F- 1H-200F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00027.12	24H-70F- 2H-150F-

66924 ADHESIVE LEFKOWELD 157
MANF: LEFFINGWELL CHEM CO
....NO TEST DATA AVAILABLE....

66925 ADHESIVE LEFKOWELD 209
MANF: LEFFINGWELL CHEM CO
....NO TEST DATA AVAILABLE....

66926 ADHESIVE LEFKOWELD 211
MANF: LEFFINGWELL CHEM CO
....NO TEST DATA AVAILABLE....

66927 ADHESIVE LEFKOWELD 218-5
MANF: LEFFINGWELL CHEM CO
....NO TEST DATA AVAILABLE....

66928 ADHESIVE LEFKOWELD 221
MANF: LEFFINGWELL CHEM CO
....NO TEST DATA AVAILABLE....

62723 ADHESIVE LEFKOWELD 46/52 EPOXY GID: ABBGXX
MANF: LEFFINGWELL CHEM CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.040	0.040	00.00	00.00	NONE
I	1	030.0	010.0	0.013	0.003	00.30	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.00	.19	.00	8H-46F- 1H-149F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00022.83	24H-70F- 24H-150F-

60358 ADHESIVE LEKUTHERM X227 GID: ABXXXX
MANF: A G BAUER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.90	.02	.00	24H-122F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

65907 ADHESIVE LGA1
MANF: BACON
....NO TEST DATA AVAILABLE....

67607 ADHESIVE LIGHTWELD 183
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005294 0

67608 ADHESIVE LIGHTWELD 184
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

67609 ADHESIVE LIGHTWELD 185
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

67610 ADHESIVE LIGHTWELD 305
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

67599 ADHESIVE LIGHTWELD 401
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

67613 ADHESIVE LIGHTWELD 432
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

67601 ADHESIVE LIGHTWELD 458
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

69628 ADHESIVE LIGHTWELD 481
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67603 ADHESIVE LIGHTWELD 625
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

67605 ADHESIVE LIGHTWELD 911
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

67606 ADHESIVE LIGHTWELD 912
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

80057 ADHESIVE LOCTITE 221
MANF: LOCTITE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	0.559	

06354 ADHESIVE LOCTITE 222-41 GID: DPCRXX
MANF: LOCTITE CORP
SPEC: ST30L682-05

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.011	0.010	00.08	12.00	T NONE
C	1	025.9	014.3	0.011	0.010	03.07	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.0E-6	21.67	9.53		24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00021.54	24H-70F- 24H-150F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005295 2

06355 ADHESIVE LOCTITE 222/GR-T PRIMER GID: DPCRXX
MANF: LOCTITE CORP

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		X	MECH	100	10	250	0.002	02	05

61630 ADHESIVE LOCTITE 241 GID: DPXXXX
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

20485 ADHESIVE LOCTITE 242 GID: ABXXXX
MANF: LOCTITE CORP SPEC: ST30L682-02/ILC

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	025.9	014.3	0.011	0.010	00.07	12.00	T NONE	No test data		No test data							
C	1	025.9	014.3	0.011	0.010	02.83	12.00	T NONE										

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.0E-6	16.43	7.45	.00	72H-25F-		B	00019.82	24H-70F- 24H-150F-

66930 ADHESIVE LOCTITE 262
MANF: LOCTITE CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.0E-6	4.43	.18	.00	72H-70F-	No test data			

64870 ADHESIVE LOCTITE 270
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

20351 ADHESIVE LOCTITE 271 THREADLOCK GID: DPXXXX
MANF: LOCTITE CORP SPEC: ST30L682-03 ST36L918-03

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	025.9	014.3	0.016	0.010	00.04	12.00	T NONE	No test data		No test data							
C	1	025.9	014.3	0.016	0.010	01.67	12.00	T NONE										

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.0E-6	13.40	1.94	.00	24H-46F- 24H-151F-		X	00019.85	24H-150F- 24H-70F-ONE COAT WAS APPLIED OVER CURED PRIMER THEN THE SUBSTRATES PLACED BETWEEN TEFLON-LINED AL PLATES.

66931 ADHESIVE LOCTITE 277
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

62148 ADHESIVE LOCTITE 290 GID: DPXXXX
MANF: LOCTITE CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.0E-6	5.19	.02	.00	24H-70F-	No test data			

05560 ADHESIVE LOCTITE 306 ACRYLIC GID: DPXXXX
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005296 4

67546 ADHESIVE LOCTITE 324
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

67547 ADHESIVE LOCTITE 326
MANF: LOCTITE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.75	.08	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05957 ADHESIVE LOCTITE 416 CYANOACRYLIC GID: DPCBXX
MANF: LOCTITE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.004	0.003		02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.6E-6	1.72	.00		24H-70F- 24H-150F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A B	00001.13	24H-70F-

62178 ADHESIVE LOCTITE 493 GID: ABXXXX
MANF: LOCTITE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	6.0E-6	4.56	.00		24H-70F- 24H-150F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

62179 ADHESIVE LOCTITE 495 GID: ABXXXX
MANF: LOCTITE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	7.6E-6	2.73	.09		24H-70F- 24H-150F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

20484 ADHESIVE LOCTITE 504 GID: ABXXXX
MANF: LOCTITE CORP SPEC: ST30L682-01/ILC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.006	0.010	00.05	12.00	T NONE
C	1	025.9	014.3	0.006	0.010	01.40	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	8.0E-6	36.01	14.58		24H-70F- 24H-150F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A B	00022.08	24H-70F- 24H-150F-

62180 ADHESIVE LOCTITE 515 GID: DPXXXX
MANF: LOCTITE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	7.6E-6	6.32	.14		24H-70F- 24H-150F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

60800 ADHESIVE LOCTITE 601 EPOXY GID: ABBGXX
MANF: LOCTITE CORP SPEC: MIL-R-46082T1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.21	.02	.00	24H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
X	00001.75	24H-70F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005297 6

66932 ADHESIVE LOCTITE 609
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

66933 ADHESIVE LOCTITE 620
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

85358 ADHESIVE LOCTITE 635
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

66934 ADHESIVE LOCTITE 680
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

69917 ADHESIVE LOCTITE 69 HYDRAULIC SEALANT GID: ABXXXX
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

60243 ADHESIVE LOCTITE 747-56 GID: DPXXXX
MANF: THOMAS & BATTS
....NO TEST DATA AVAILABLE....

61414 ADHESIVE LOCTITE 75 GID: XXXX
MANF: LOCTITE CORP SPEC: MIL-R-46082T1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.5E-6	13.91	.71		24H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
A	X 00002.54	24H-70F- 24H-150F-

TOXICITY

62181 ADHESIVE LOCTITE 80092 SUPERGLUE GID: ABXXXX
MANF: LOCTITE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.97	.04	.00	24H-46F- 24H-151F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62182 ADHESIVE LOCTITE 80414 LOCKNUTS GID: ABXXXX
MANF: LOCTITE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	18.79	7.82	.00	24H-151F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62172 ADHESIVE LOCTITE 80418 GID: ABXXXX
MANF: LOCTITE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.6E-6	7.15	.32		24H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62171 ADHESIVE LOCTITE 80426 GID: ABXXXX
MANF: LOCTITE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.6E-6	18.89	3.01		24H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005298 8

62149 ADHESIVE LOCTITE 80477 GID: DPXXXX
MANF: LOCTITE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	6.10	.46		24H-70F- 24H-150F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

61413 ADHESIVE LOCTITE A GID: DSXXXX
MANF: LOCTITE CORP
SPEC: MIL-S-22473D

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.54	.03	.00	24H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00000.84	168H-70F-

80063 ADHESIVE LOCTITE AV
MANF: NIPPON ROCKTIGHT CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	X 1.542	

63526 ADHESIVE LOCTITE BLACK MAX GID: ABXXXX
MANF: LOCTITE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	030.0	010.0	0.001	0.003	00.00	00.00	NONE
B	1	030.0	010.0	0.001	0.003	03.90	06.87	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00004.14	72H-70F-

61415 ADHESIVE LOCTITE E/LOCTITE T PRIMER GID: DPCBXX
MANF: LOCTITE CORP
SPEC: MIL-A-907

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	250	10	70	0.001	00	20
B	PNEU	500		250		0	20
X	MECH	500	72	70	0.001	1	03
B	PNEU	500		70	0.002	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.7E-6	9.90	7.68		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00004.64	24H-70F- 24H-150F-

60809 ADHESIVE LOCTITE HV GID: DSXXXX
MANF: LOCTITE CORP
SPEC: MIL-S-22473

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00001.10	168H-70F-

60797 ADHESIVE LOCTITE LO555 GID: DPXXXX
MANF: LOCTITE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1500	72	-297	0.007	0	20
B	MECH	1500	72	70	0.007	0	20
I	MECH	3000	72	70	0.007	0	01
I	PNEU	4000		70	0.060	0	01
I	PNEU	5000		70	0.060	0	03

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005299 T

60797 ADHESIVE LOCTITE LO555 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	6000	72	70	0.050	0	20
B	PNEU	6000		70	0.060	0	20

66935 ADHESIVE LOCTITE QUICK-SET ADHESIVE 404
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

20216 ADHESIVE LOCTITE SCREWLOCK/T PRIMER GID: DPXXXX
MANF: LOCTITE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00001.11	.05H-70F- 168H-70F-

67549 ADHESIVE LOCTITE ULTRA PERFORMANCE TAX PAK
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

66370 ADHESIVE M P A MARK II
MANF: DIMITER EMULSION & CHEMICAL
....NO TEST DATA AVAILABLE....

66366 ADHESIVE M P A MARK II 1087
MANF: DIMITER EMULSION & CHEMICAL
....NO TEST DATA AVAILABLE....

66367 ADHESIVE M P A MARK II 1095
MANF: DIMITER EMULSION & CHEMICAL
....NO TEST DATA AVAILABLE....

60415 ADHESIVE M-BOND GID: ABXXXX
MANF: MICRO MEASUREMENTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.98	.00	.00	SEE TEST REPORT

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

60228 ADHESIVE M-BOND 200 GID: ABXXXX
MANF: MICRO MEASUREMENTS SPEC: STW5-2970

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	14.34	.01		12H-70F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

67539 ADHESIVE M-BOND 43B
MANF: MICRO MEASUREMENTS
....NO TEST DATA AVAILABLE....

60199 ADHESIVE M-BOND 600 GID: ABBGXX
MANF: MICRO MEASUREMENTS SPEC: STM0710-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		01.80	NONE
I	1	025.9	014.3	0.034		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	4.18	.01	.67	2H-250F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	0.56	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005300 2

05129 ADHESIVE M-BOND 610 GID: ABBGXX
MANF: MICRO MEASUREMENTS SPEC: MBO120-081T1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.3E-7	.53	.08		1H-350F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00000.99	2H-250F-

67542 ADHESIVE M-BOND A12
MANF: MICRO MEASUREMENTS
....NO TEST DATA AVAILABLE....

67541 ADHESIVE M-BOND AE15
MANF: MICRO MEASUREMENTS
....NO TEST DATA AVAILABLE....

67538 ADHESIVE M-BOND GA100
MANF: MICRO MEASUREMENTS
....NO TEST DATA AVAILABLE....

67537 ADHESIVE M-BOND GA2
MANF: MICRO MEASUREMENTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.13	.77	.00	48H-70F-
					24H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

67540 ADHESIVE M-BOND GA61
MANF: MICRO MEASUREMENTS
....NO TEST DATA AVAILABLE....

66443 ADHESIVE M336
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

66442 ADHESIVE M500
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

60269 ADHESIVE M6704 EPOXY GID: ABBGXX
MANF: DENNIS CHEMICAL
....NO TEST DATA AVAILABLE....

66371 ADHESIVE M90
MANF: DIMITER EMULSION & CHEMICAL
....NO TEST DATA AVAILABLE....

66729 ADHESIVE MACCO AW40
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66730 ADHESIVE MACCO BL70
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66731 ADHESIVE MACCO C5
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005301 4

66732 ADHESIVE MACCO CA80
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66733 ADHESIVE MACCO CA90
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66734 ADHESIVE MACCO CERAMIC WALL TILE ADHESIVE M111
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66735 ADHESIVE MACCO LIQUID NAILS LN60
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66736 ADHESIVE MACCO LIQUID NAILS LN601
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66737 ADHESIVE MACCO LIQUID NAILS LN602
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66738 ADHESIVE MACCO LIQUID NAILS LN603
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66739 ADHESIVE MACCO LUQUID ROOF REPAIR LR808
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66740 ADHESIVE MACCO LUQUID WEATHER STRIP LN165
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66741 ADHESIVE MACCO M112
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66742 ADHESIVE MACCO M220
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66743 ADHESIVE MACCO M221
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66744 ADHESIVE MACCO PV20
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66745 ADHESIVE MACCO RC711
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005302 6 ■

Information Handling Services, 2000

66746 ADHESIVE MACCO SB60
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66747 ADHESIVE MACCO TA605
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66748 ADHESIVE MACCO WG166
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

66749 ADHESIVE MACCO WOODWORKERS' GLUE
MANF: GLIDDEN
....NO TEST DATA AVAILABLE....

65945 ADHESIVE MAINTZ N1000
MANF: BONDED PRODUCTS
....NO TEST DATA AVAILABLE....

65627 ADHESIVE MARASET RESIN 532C
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

65628 ADHESIVE MARASET RESIN 532F
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

65629 ADHESIVE MARASET RESIN 536
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

65630 ADHESIVE MARASET RESIN 537
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67645 ADHESIVE MARK 10
MANF: POLY-CARB

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.76	.02	2.26	24H-46F- 168H-46F-	No test data		

67646 ADHESIVE MARK 10.3
MANF: POLY-CARB
....NO TEST DATA AVAILABLE....

67647 ADHESIVE MARK 19
MANF: POLY-CARB
....NO TEST DATA AVAILABLE....

85064 ADHESIVE MARK 231 EPOXY PUTTY
MANF: POLY-CARB
....NO TEST DATA AVAILABLE....

67648 ADHESIVE MARK 24
MANF: POLY-CARB
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005303 8

67649 ADHESIVE MARK 25
MANF: POLY-CARB
....NO TEST DATA AVAILABLE....

67650 ADHESIVE MARK 25.3
MANF: POLY-CARB
....NO TEST DATA AVAILABLE....

67651 ADHESIVE MARK 29
MANF: POLY-CARB
....NO TEST DATA AVAILABLE....

67644 ADHESIVE MARK 3
MANF: POLY-CARB
....NO TEST DATA AVAILABLE....

67652 ADHESIVE MARK 30
MANF: POLY-CARB
....NO TEST DATA AVAILABLE....

67653 ADHESIVE MARK 30.1
MANF: POLY-CARB
....NO TEST DATA AVAILABLE....

85076 ADHESIVE MARK 8
MANF: POLY-CARB
....NO TEST DATA AVAILABLE....

66137 ADHESIVE MASTIC EPOXY
MANF: COMMERCIAL CHEMICAL
....NO TEST DATA AVAILABLE....

81233 ADHESIVE MB302
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81235 ADHESIVE MB303
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

61334 ADHESIVE MEL 20 GID: ABXXXX
MANF: HUGHES AIRCRAFT

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.47	.00			No test data		

67103 ADHESIVE MELTHENE M1310
MANF: NORTHERN PETROCHEMICAL CO
....NO TEST DATA AVAILABLE....

67098 ADHESIVE MELTHENE M5001
MANF: NORTHERN PETROCHEMICAL CO
....NO TEST DATA AVAILABLE....

67099 ADHESIVE MELTHENE M5002
MANF: NORTHERN PETROCHEMICAL CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005304 T ■

67100 ADHESIVE MELTHENE M5004
MANF: NORTHERN PETROCHEMICAL CO
....NO TEST DATA AVAILABLE....

67101 ADHESIVE MELTHENE M5030
MANF: NORTHERN PETROCHEMICAL CO
....NO TEST DATA AVAILABLE....

67102 ADHESIVE MELTHENE M5311
MANF: NORTHERN PETROCHEMICAL CO
....NO TEST DATA AVAILABLE....

67104 ADHESIVE MELTHENE M5331
MANF: NORTHERN PETROCHEMICAL CO
....NO TEST DATA AVAILABLE....

67105 ADHESIVE MELTHENE M5400
MANF: NORTHERN PETROCHEMICAL CO
....NO TEST DATA AVAILABLE....

66980 ADHESIVE MERECO "GDO"
MANF: MERECO
....NO TEST DATA AVAILABLE....

67043 ADHESIVE MERECO 302
MANF: MERECO
....NO TEST DATA AVAILABLE....

66981 ADHESIVE MERECO 3446
MANF: MERECO
....NO TEST DATA AVAILABLE....

66982 ADHESIVE MERECO 3808
MANF: MERECO
....NO TEST DATA AVAILABLE....

67034 ADHESIVE MERECO CN773 WITH 16C
MANF: MERECO
....NO TEST DATA AVAILABLE....

67033 ADHESIVE MERECO CN773 WITH 16E
MANF: MERECO
....NO TEST DATA AVAILABLE....

67036 ADHESIVE MERECO CN934
MANF: MERECO
....NO TEST DATA AVAILABLE....

67037 ADHESIVE MERECO CN967
MANF: MERECO
....NO TEST DATA AVAILABLE....

67053 ADHESIVE MERECO METASIL 5002
MANF: MERECO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005305 1

Information Handling Services, 2000

67054 ADHESIVE MERECO METASIL 5004
MANF: MERECO
....NO TEST DATA AVAILABLE....

67039 ADHESIVE MERECO METASIL 5008
MANF: MERECO
....NO TEST DATA AVAILABLE....

67055 ADHESIVE MERECO METASIL RTV 5005
MANF: MERECO
....NO TEST DATA AVAILABLE....

67056 ADHESIVE MERECO METASIL XL152
MANF: MERECO
....NO TEST DATA AVAILABLE....

67020 ADHESIVE MERECO SCN568
MANF: MERECO
....NO TEST DATA AVAILABLE....

66983 ADHESIVE MERECO SN631
MANF: MERECO
....NO TEST DATA AVAILABLE....

66984 ADHESIVE MERECO SN632
MANF: MERECO
....NO TEST DATA AVAILABLE....

66985 ADHESIVE MERECO SN781
MANF: MERECO
....NO TEST DATA AVAILABLE....

66986 ADHESIVE MERECO XL225
MANF: MERECO
....NO TEST DATA AVAILABLE....

66987 ADHESIVE MERECO XL294
MANF: MERECO
....NO TEST DATA AVAILABLE....

67048 ADHESIVE MERECO XL295
MANF: MERECO
....NO TEST DATA AVAILABLE....

66988 ADHESIVE MERECO XL330
MANF: MERECO
....NO TEST DATA AVAILABLE....

67019 ADHESIVE MERECO XL342
MANF: MERECO
....NO TEST DATA AVAILABLE....

66989 ADHESIVE MERECO XL354
MANF: MERECO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005306 3

Information Handling Services, 2000

66990 ADHESIVE MERECO XL373
MANF: MERECO
....NO TEST DATA AVAILABLE....

66991 ADHESIVE MERECO XL389
MANF: MERECO
....NO TEST DATA AVAILABLE....

66992 ADHESIVE MERECO XL389T
MANF: MERECO
....NO TEST DATA AVAILABLE....

66993 ADHESIVE MERECO XLN557
MANF: MERECO
....NO TEST DATA AVAILABLE....

66994 ADHESIVE MERECO XLN420/CATALYST 16E
MANF: MERECO
....NO TEST DATA AVAILABLE....

66995 ADHESIVE MERECO XLN420/CATALYST XL380
MANF: MERECO
....NO TEST DATA AVAILABLE....

66996 ADHESIVE MERECO XLN420/CATALYST XLN474
MANF: MERECO
....NO TEST DATA AVAILABLE....

67031 ADHESIVE MERECO XLN425
MANF: MERECO
....NO TEST DATA AVAILABLE....

81256 ADHESIVE MERECO XLN442
MANF: MERECO
....NO TEST DATA AVAILABLE....

67057 ADHESIVE MERECO XLN449
MANF: MERECO
....NO TEST DATA AVAILABLE....

67032 ADHESIVE MERECO XLN455
MANF: MERECO
....NO TEST DATA AVAILABLE....

66997 ADHESIVE MERECO XLN470
MANF: MERECO
....NO TEST DATA AVAILABLE....

66998 ADHESIVE MERECO XLN490
MANF: MERECO
....NO TEST DATA AVAILABLE....

67021 ADHESIVE MERECO XLN589
MANF: MERECO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005307 5

67018 ADHESIVE METACAST 1201
MANF: MERECO
....NO TEST DATA AVAILABLE....

67038 ADHESIVE METACAST 5448 WITH #10
MANF: MERECO
....NO TEST DATA AVAILABLE....

67016 ADHESIVE METACAST 5448 WITH 16E
MANF: MERECO
....NO TEST DATA AVAILABLE....

67017 ADHESIVE METACAST 5448 WITH 43
MANF: MERECO
....NO TEST DATA AVAILABLE....

67022 ADHESIVE METADUCT 1201 CN611
MANF: MERECO
....NO TEST DATA AVAILABLE....

67023 ADHESIVE METADUCT 1202
MANF: MERECO
....NO TEST DATA AVAILABLE....

67024 ADHESIVE METADUCT 1204
MANF: MERECO
....NO TEST DATA AVAILABLE....

67050 ADHESIVE METADUCT 1206
MANF: MERECO
....NO TEST DATA AVAILABLE....

67025 ADHESIVE METADUCT 1206 SG3
MANF: MERECO
....NO TEST DATA AVAILABLE....

67026 ADHESIVE METADUCT 1206 SG4
MANF: MERECO
....NO TEST DATA AVAILABLE....

67027 ADHESIVE METADUCT 1212
MANF: MERECO
....NO TEST DATA AVAILABLE....

67028 ADHESIVE METADUCT 1216 SERIES
MANF: MERECO
....NO TEST DATA AVAILABLE....

67029 ADHESIVE METADUCT 1216-1
MANF: MERECO
....NO TEST DATA AVAILABLE....

67030 ADHESIVE METADUCT 1216-2
MANF: MERECO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005308 7 ■

Information Handling Services, 2000

67044 ADHESIVE METADUCT 1225 SN736
MANF: MERECO
....NO TEST DATA AVAILABLE....

67045 ADHESIVE METADUCT 1225 SN742
MANF: MERECO
....NO TEST DATA AVAILABLE....

67046 ADHESIVE METADUCT 1225 XL245
MANF: MERECO
....NO TEST DATA AVAILABLE....

67047 ADHESIVE METADUCT XL126
MANF: MERECO
....NO TEST DATA AVAILABLE....

67049 ADHESIVE METADUCT XLN583 MOD 1
MANF: MERECO
....NO TEST DATA AVAILABLE....

67000 ADHESIVE METAGRIP 321
MANF: MERECO
....NO TEST DATA AVAILABLE....

66999 ADHESIVE METALINK 361
MANF: MERECO
....NO TEST DATA AVAILABLE....

65428 ADHESIVE METALSET A4 EPOXY GID: ABBGXX
MANF: SMOOTH-ON INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.010	0.003	00.40	06.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00021.67	

05299 ADHESIVE METASET BLUE LABEL GID: ABXXXX
....NO TEST DATA AVAILABLE....

80272 ADHESIVE METHACRYLATE MX611 GID: ABXXXX
MANF: DEVCON CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	7.0E-6	6.01	.17	.36	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

66053 ADHESIVE METLBOND 1113
MANF: CELANESE
....NO TEST DATA AVAILABLE....

60339 ADHESIVE METLBOND 1133 FOAM GID: ABBGXX
MANF: NARMCO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.04	.04	.00	.42H-300F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005309 9

60365 ADHESIVE METLBOND 306/112 FOAM GID: ABBGXX
MANF: NARMCO
....NO TEST DATA AVAILABLE....

64895 ADHESIVE METLBOND 328 GID: ACBGXX
MANF: NARMCO SPEC: MIL-A-25463

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.12	.10	.00	1.5H-329F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05106 ADHESIVE METLBOND 329 EPOXY FILM GID: ABBGXX
MANF: NARMCO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.28	.01	.00	1H-350F-0psia

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66054 ADHESIVE METLBOND 329-7
MANF: CELANESE
....NO TEST DATA AVAILABLE....

05092 ADHESIVE METLBOND 6607 FOAM EPOXY GID: ABBGBX
MANF: NARMCO SPEC: MB0120-077

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.107			00.10	NONE
C	1	023.8	014.5	0.107		00.20	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.8E-7	.95	.01		

ODOR

RT	RT WEIGHT	CURE
A	K 00100.50	

TOXICITY

67001 ADHESIVE METREGRIP 302
MANF: MERECO
....NO TEST DATA AVAILABLE....

05582 ADHESIVE METREGRIP 303 GID: ABXXXX
MANF: MERECO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.010	0.003	00.20	12.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	B 00022.98	.5H-150F-

TOXICITY

67002 ADHESIVE METREGRIP 303MV
MANF: MERECO
....NO TEST DATA AVAILABLE....

67003 ADHESIVE METREGRIP 303VLV
MANF: MERECO
....NO TEST DATA AVAILABLE....

67004 ADHESIVE METREGRIP 30LV
MANF: MERECO
....NO TEST DATA AVAILABLE....

67011 ADHESIVE METREGRIP 312
MANF: MERECO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005310 5 ■

67005 ADHESIVE METREGRIP 315
MANF: MERECO
....NO TEST DATA AVAILABLE....

67006 ADHESIVE METREGRIP 321
MANF: MERECO
....NO TEST DATA AVAILABLE....

67007 ADHESIVE METREGRIP 3446
MANF: MERECO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.50	.00	.00	2H-199F- 16H-399F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

67008 ADHESIVE METREGRIP 355
MANF: MERECO
....NO TEST DATA AVAILABLE....

67009 ADHESIVE METREGRIP 385-1
MANF: MERECO
....NO TEST DATA AVAILABLE....

67010 ADHESIVE METREGRIP 385-2
MANF: MERECO
....NO TEST DATA AVAILABLE....

67051 ADHESIVE METRESET 3661
MANF: MERECO
....NO TEST DATA AVAILABLE....

67052 ADHESIVE METRESET 3662
MANF: MERECO
....NO TEST DATA AVAILABLE....

67416 ADHESIVE MICROCIRCUIT SILVER TYPE K
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67417 ADHESIVE MICROCIRCUIT SILVER TYPE L
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67418 ADHESIVE MICROCIRCUIT SILVER TYPE M
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67419 ADHESIVE MICROCIRCUIT SILVER TYPE O
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

60449 ADHESIVE MINCO 21365/7-1 GID: ABBGXX
MANF: MINCO PRODUCTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.46	.10		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005311 7 ■

67059 ADHESIVE MIRACLE 40 PLUS
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67060 ADHESIVE MIRACLE ALL PURPOSE CONSTRUCTION ADHESIVE
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67061 ADHESIVE MIRACLE BLACK MAGIC TYPE "M"
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67062 ADHESIVE MIRACLE CA25
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67063 ADHESIVE MIRACLE CEILING TILE ADHESIVE
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

81258 ADHESIVE MIRACLE CLEAR SEALANT
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67064 ADHESIVE MIRACLE CONTACT CEMENT
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67066 ADHESIVE MIRACLE D518
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67065 ADHESIVE MIRACLE D617
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

81261 ADHESIVE MIRACLE D618
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67067 ADHESIVE MIRACLE DSA20
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67068 ADHESIVE MIRACLE DSA40
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67069 ADHESIVE MIRACLE GAUGED SLATE ADHESIVE
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67070 ADHESIVE MIRACLE HT4620
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005312 9

Information Handling Services, 2000

67071 ADHESIVE MIRACLE L2000N FACING ADHESIVE
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67072 ADHESIVE MIRACLE L3000 FACING ADHESIVE
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67073 ADHESIVE MIRACLE LA69
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67074 ADHESIVE MIRACLE LA76
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67075 ADHESIVE MIRACLE LATEX CAULK 'N GLUE
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67076 ADHESIVE MIRACLE MA200
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67077 ADHESIVE MIRACLE MA222
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67078 ADHESIVE MIRACLE MA76
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67079 ADHESIVE MIRACLE MS120
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67080 ADHESIVE MIRACLE MS130 "SAFE 'N SOUND"
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67081 ADHESIVE MIRACLE NON-FLAMMABLE CONTACT CEMENT
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67082 ADHESIVE MIRACLE PANEL FOAM AND CONSTRUCTION ADHESIVE
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67083 ADHESIVE MIRACLE PF101
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67084 ADHESIVE MIRACLE PF102
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005313 0

67085 ADHESIVE MIRACLE PF88
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67086 ADHESIVE MIRACLE PF92
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67087 ADHESIVE MIRACLE PF95
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67088 ADHESIVE MIRACLE PF97
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67089 ADHESIVE MIRACLE RESIN NP428
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

81263 ADHESIVE MIRACLE SCS100
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67090 ADHESIVE MIRACLE SPA66
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67091 ADHESIVE MIRACLE WALLBOARD ADHESIVE
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

67058 ADHESIVE MIRAPOXY MA800
MANF: MIRACLE ADHESIVES CORP
....NO TEST DATA AVAILABLE....

06205 ADHESIVE MPC52 A/B EPOXY GID: BABGHO
MANF: GENERAL ELECTRIC SPEC: GE171A8299 TYIN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
C	2	020.9	014.7	0.021	0.003	00.00	00.00		NONE
C	1	020.9	014.7	0.021	0.003	00.16	12.00	T	NONE
C	2	025.9	014.3	0.021	0.003	00.00	00.00		NONE
C	1	025.9	014.3	0.021	0.003	00.23	12.00	T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-7	.71	.03		4H-70F- 2H-145F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00020.53	4H-70F- 2H-145F-

66618 ADHESIVE MULTIBOND AP1 WITH CAT A
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66619 ADHESIVE MULTIBOND B
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005314 2

66620 ADHESIVE MULTIBOND C
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66621 ADHESIVE MULTIBOND F
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66622 ADHESIVE MULTIBOND LT1
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66623 ADHESIVE MULTIBOND LT1 WITH CATALYST W
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66624 ADHESIVE MULTIBOND RX
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66625 ADHESIVE MULTIBOND W WITH CATALYST A
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66626 ADHESIVE MULTIBOND W WITH CATALYST W
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

65173 ADHESIVE MVP TY 33 GID: ABXXXX
MANF: DEVCON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.001	0.003		03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00003.26	8H-70F-

66721 ADHESIVE M-SIL RTV 122
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

66720 ADHESIVE M-SIL RTV 123
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

66719 ADHESIVE M-SIL RTV 128
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

67192 ADHESIVE M134
MANF: STABOND CORP
....NO TEST DATA AVAILABLE....

60506 ADHESIVE M136 GID: ABDBXX
MANF: SHORE-UBS CHEM CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.004	0.003		02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005315 4

60506 ADHESIVE N136 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	033.0	014.3	0.004	0.003		02.80	NONE
C	1	100.0	020.2	0.005	0.003	01.85	12.00	T NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.41	.45	.00	24H-46F-

ODOR

RT	RT	WEIGHT	CURE
A	V	00003.76	

TOXICITY

66709 ADHESIVE N6H
MANF: GATES ENGINEERING CO INC
....NO TEST DATA AVAILABLE....

66710 ADHESIVE N7
MANF: GATES ENGINEERING CO INC
....NO TEST DATA AVAILABLE....

61348 ADHESIVE NEOPRENE 61015 GID: ABDBXX
MANF: HITCO
U S POLYMERIC

SPEC: MB0120-023 MB0120-025

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.003	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.003	0.003		01.40	NONE
A	1	030.0	009.0	0.004	0.003		03.70	NONE
A	1	030.0	009.0	0.003	0.003		03.90	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.22	.12	.00	168H-46F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60723 ADHESIVE NEOPRENE E2084 GID: ABDBXX
MANF: AMERICAN FINISH & CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	X	00012.27	168H-70F-

TOXICITY

67434 ADHESIVE NICKEL BOND TYPE 40
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67435 ADHESIVE NICKEL BOND TYPE 50
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67436 ADHESIVE NICKEL BOND TYPE 60
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

66865 ADHESIVE OMNIFIT 1150
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66866 ADHESIVE OMNIFIT 1350
MANF: HENKEL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005316 6

66867 ADHESIVE OMNIFIT 1550
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66868 ADHESIVE OMNIFIT 1570
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66869 ADHESIVE OMNIFIT 1710
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66870 ADHESIVE OMNIFIT 1730
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66871 ADHESIVE OMNIFIT 1750
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66872 ADHESIVE OMNIFIT 1790
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66873 ADHESIVE OMNIFIT INSTANT GASKET 10
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66874 ADHESIVE OMNIFIT INSTANT GASKET 20
MANF: HENKEL
....NO TEST DATA AVAILABLE....

20403 ADHESIVE OPTICAL CEMENT GID: ABBGXX

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	10.89	.05	10.11		No test data		

84071 ADHESIVE OUTPUT 315
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

84072 ADHESIVE OUTPUT 383
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

84073 ADHESIVE OUTPUT 384
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

67550 ADHESIVE OUTPUT THERMAL CONDUCTIVE ADHESIVE
MANF: LOCTITE CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.30	.01	.00	1H-70F- 4H-140F-	No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005317 8

67551 ADHESIVE OUTPUT THERMAL CONDUCTIVE ADHESIVE REPAIRABLE
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

67200 ADHESIVE P/N 72-00008
MANF: TECKNIT
....NO TEST DATA AVAILABLE....

82252 ADHESIVE P/S 700
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82253 ADHESIVE P/S 706A
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82254 ADHESIVE P/S 706B1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82255 ADHESIVE P/S 706B2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82256 ADHESIVE P/S 714
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82262 ADHESIVE P/S 870-2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82258 ADHESIVE P/S 870A1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82259 ADHESIVE P/S 870A2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82260 ADHESIVE P/S 870B1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82257 ADHESIVE P/S 870C
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82263 ADHESIVE P/S 870C12
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82261 ADHESIVE P/S 870C24
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005318 T ■

Information Handling Services, 2000

Information Handling Services, 2000

82264 ADHESIVE P/S 872B1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82265 ADHESIVE P/S 872B2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82266 ADHESIVE P/S 881-1/6
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82268 ADHESIVE P/S 888-2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82267 ADHESIVE P/S 888D1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82269 ADHESIVE P/S 890A1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82270 ADHESIVE P/S 890A2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82271 ADHESIVE P/S 890B1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82272 ADHESIVE P/S 890B4
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82273 ADHESIVE P/S 898B8
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82274 ADHESIVE P/S 898D2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82275 ADHESIVE P/S 899A1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82276 ADHESIVE P/S 899A2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82277 ADHESIVE P/S 899B1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005319 1 ■

82278 ADHESIVE P/S 899B1/4
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82279 ADHESIVE P/S 899B2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82280 ADHESIVE P/S 899B4
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82281 ADHESIVE P/S 899B6
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

66524 ADHESIVE P602
MANF: ETHERINGTON/U S PROLAM
....NO TEST DATA AVAILABLE....

66525 ADHESIVE P650
MANF: ETHERINGTON/U S PROLAM
....NO TEST DATA AVAILABLE....

66526 ADHESIVE P670I
MANF: ETHERINGTON/U S PROLAM
....NO TEST DATA AVAILABLE....

66527 ADHESIVE P680
MANF: ETHERINGTON/U S PROLAM
....NO TEST DATA AVAILABLE....

60438 ADHESIVE P75 FOAM GID: ABBGXX
MANF: BACON
SPEC: MC7609-01

FLAMMABILITY								FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.250			01.50	NONE	No test data	No test data						

20163 ADHESIVE P82 C GID: ABBGXX
MANF: BACON
SPEC: MC287-00540001

FLAMMABILITY								FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.020			05.03	SMALL	No test data	No test data						

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	3.6E-7	.18	.01		2H-257F- 1H-70F-

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

67347 ADHESIVE PA4887
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67277 ADHESIVE PALLETING ADHESIVE EC4650
MANF: 3M CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005320 8

67560 ADHESIVE PANEL AND FOAM #104
MANF: 3M CO
....NO TEST DATA AVAILABLE....

66131 ADHESIVE PANELGRIP 1229
MANF: COLUMBIA CEMENT
....NO TEST DATA AVAILABLE....

67204 ADHESIVE PARALAC DPB278
MANF: TESTWORTH LABS
....NO TEST DATA AVAILABLE....

67205 ADHESIVE PARALAC RC57
MANF: TESTWORTH LABS
....NO TEST DATA AVAILABLE....

80525 ADHESIVE PEN SEAL 50
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

67117 ADHESIVE PERMABOND 101
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67118 ADHESIVE PERMABOND 102
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67119 ADHESIVE PERMABOND 105
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

84975 ADHESIVE PERMABOND 107
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

84978 ADHESIVE PERMABOND 108
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67120 ADHESIVE PERMABOND 130
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

60685 ADHESIVE PERMABOND 200 GID: AEXXXX
MANF: PERMABOND SPEC: MIL-A-46050CT1

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							X	00006.00	24H-70F-

67121 ADHESIVE PERMABOND 240
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

84979 ADHESIVE PERMABOND 268
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005321 T

84981 ADHESIVE PERMABOND 747
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67122 ADHESIVE PERMABOND 750
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

84983 ADHESIVE PERMABOND ESP108
MANF: PERMABOND

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.65	.01	.43	.75H-302F-

ODOR			TOXICITY
RT	RT WEIGHT	CURE	
No test data			

84985 ADHESIVE PERMABOND ESP109
MANF: PERMABOND

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.51	.00	.35	.75H-302F-

ODOR			TOXICITY
RT	RT WEIGHT	CURE	
No test data			

84988 ADHESIVE PERMABOND ESP110
MANF: PERMABOND

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.69	.03	.48	.75H-302F-

ODOR			TOXICITY
RT	RT WEIGHT	CURE	
No test data			

62078 ADHESIVE PERMACEL KAPTON GID: ABDKXX
MANF: PERMACEL

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
I	5.2E-7	1.04	.52		

ODOR			TOXICITY
RT	RT WEIGHT	CURE	
No test data			

67124 ADHESIVE PERMALOK 5M060
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67112 ADHESIVE PERMALOK AL138
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67110 ADHESIVE PERMALOK HH120
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

84966 ADHESIVE PERMALOK HH190
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

84993 ADHESIVE PERMALOK HH194
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

84995 ADHESIVE PERMALOK HH195
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005322 1

67111 ADHESIVE PERMALOK HL126
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67113 ADHESIVE PERMALOK HM118
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67114 ADHESIVE PERMALOK HM128
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67115 ADHESIVE PERMALOK LM113
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

84970 ADHESIVE PERMALOK MM115
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67116 ADHESIVE PERMALOK MM15
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

84973 ADHESIVE PERMALOK PAS10
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

81863 ADHESIVE PL410
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81864 ADHESIVE PL420
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81865 ADHESIVE PL425 EPOXY
MANF: B F GOODRICH

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7	0.125	0.020	00.03	7.75	NONE	No test data		No test data							

85429 ADHESIVE PL430X EPOXY GID: ABXXXX
MANF: B F GOODRICH

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7	0.087	0.020	00.02	12.0	T MOD	No test data		No test data							

66764 ADHESIVE PL601
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66765 ADHESIVE PL601 W/P FILM
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005323 3

66766 ADHESIVE PL603
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66767 ADHESIVE PL604
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66768 ADHESIVE PL605
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66769 ADHESIVE PL606
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66770 ADHESIVE PL618-1
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66771 ADHESIVE PL618-2
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66772 ADHESIVE PL639 N/P FILM
MANF: B F GOODRICH

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.12	.16	.42	2H-360F-	No test data		

66773 ADHESIVE PL651
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66774 ADHESIVE PL653EX
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66775 ADHESIVE PL654GD
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66776 ADHESIVE PL655
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66777 ADHESIVE PL655 N/P FILM
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66778 ADHESIVE PL659
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66779 ADHESIVE PL717
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005324 5

Information Handling Services, 2000

66780 ADHESIVE PL741
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66781 ADHESIVE PL750
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66782 ADHESIVE PL751
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66783 ADHESIVE PL760
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66784 ADHESIVE PL770
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66785 ADHESIVE PL776
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

66756 ADHESIVE PL777
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81001 ADHESIVE PLASTILOCK 637
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

60693 ADHESIVE PLASTILOCK 729-3/728 GID: ABBGXX
MANF: B F GOODRICH
SPEC: ST0120-LB0001

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.018		00.00	00.00	NONE
A	1	023.8	014.5	0.018			03.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.94	.02	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00054.24	1H-350F-

05097 ADHESIVE PLASTILOCK 731 EPOXY GID: ABBGXX
MANF: B F GOODRICH
SPEC: MB0120-071

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.50	.01	.00	2H-351F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00020.29	2H-350F-40psia

80766 ADHESIVE PLASTOMERIC SEALANT
MANF: ASSOCIATED ALLIED
....NO TEST DATA AVAILABLE....

67685 ADHESIVE PLD700
MANF: EPOXYLITE CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005325 7

20311 ADHESIVE PLIOBOND GID: ABXXXX
MANF: GOODYEAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002	0.003		01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.38	.00	.00	24H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00010.94	20H-70F-

66786 ADHESIVE PLIOBOND 1000
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66787 ADHESIVE PLIOBOND 1001
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66788 ADHESIVE PLIOBOND 1005
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66789 ADHESIVE PLIOBOND 1008
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66790 ADHESIVE PLIOBOND 1012
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66791 ADHESIVE PLIOBOND 1014-44
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66792 ADHESIVE PLIOBOND 1016
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66793 ADHESIVE PLIOBOND 1018
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66794 ADHESIVE PLIOBOND 1063
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66795 ADHESIVE PLIOBOND 1177
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66796 ADHESIVE PLIOBOND 1240
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66797 ADHESIVE PLIOBOND 20
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005326 9

66798 ADHESIVE PLIOBOND 2000
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66799 ADHESIVE PLIOBOND 2001
MANF: GOODYEAR

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.41	.04	5.78	24H-46F- 168H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66800 ADHESIVE PLIOBOND 2003
MANF: GOODYEAR

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.91	.05	1.38	1H-158F- 5H-140F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66801 ADHESIVE PLIOBOND 2004
MANF: GOODYEAR

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.86	.00	.41	168H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66802 ADHESIVE PLIOBOND 2005
MANF: GOODYEAR

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.86	.00	6.44	168H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66803 ADHESIVE PLIOBOND 2007
MANF: GOODYEAR

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.30	.04	1.69	24H-46F- 168H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66804 ADHESIVE PLIOBOND 2011
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66805 ADHESIVE PLIOBOND 2014
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66806 ADHESIVE PLIOBOND 2015
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66807 ADHESIVE PLIOBOND 2021
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66808 ADHESIVE PLIOBOND 2024
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005327 0

66809 ADHESIVE PLIOBOND 2030
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66810 ADHESIVE PLIOBOND 2033
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66812 ADHESIVE PLIOBOND 2221
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66813 ADHESIVE PLIOBOND 30
MANF: GOODYEAR

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	13.55	.70	.00	48H-77F-	No test data		

66842 ADHESIVE PLIOBOND 30HT
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66814 ADHESIVE PLIOBOND 40
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66815 ADHESIVE PLIOBOND 4000
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66816 ADHESIVE PLIOBOND 4007
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66817 ADHESIVE PLIOBOND 4014
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66818 ADHESIVE PLIOBOND 4015
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66819 ADHESIVE PLIOBOND 4222
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66820 ADHESIVE PLIOBOND 4237
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66821 ADHESIVE PLIOBOND 4245
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66822 ADHESIVE PLIOBOND 4254
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005328 2

66823 ADHESIVE PLIOBOND 4275
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66824 ADHESIVE PLIOBOND 4290
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66825 ADHESIVE PLIOBOND 5000
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66826 ADHESIVE PLIOBOND 5001
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66827 ADHESIVE PLIOBOND 5002
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66828 ADHESIVE PLIOBOND 5013
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66829 ADHESIVE PLIOBOND 5015
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66830 ADHESIVE PLIOBOND 5019
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66831 ADHESIVE PLIOBOND 5037
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66832 ADHESIVE PLIOBOND 7001
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66833 ADHESIVE PLIOBOND 7003
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66834 ADHESIVE PLIOBOND 7005
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66835 ADHESIVE PLIOBOND 8000
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66836 ADHESIVE PLIOBOND 8001
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005329 4

66837 ADHESIVE PLIOBOND 8003
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66838 ADHESIVE PLIOBOND 8004
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66839 ADHESIVE PLIOBOND 8005
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66840 ADHESIVE PLIOBOND 9002
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

66841 ADHESIVE PLIOBOND 9005
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

65888 ADHESIVE PLIOGRIP 6000
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

65889 ADHESIVE PLIOGRIP 6600
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

65890 ADHESIVE PLIOGRIP 6627
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

65891 ADHESIVE PLIOGRIP 6800
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

67598 ADHESIVE POLAQUA 103L
MANF: ADM TRONICS
....NO TEST DATA AVAILABLE....

67596 ADHESIVE POLAQUA 123-07
MANF: ADM TRONICS
....NO TEST DATA AVAILABLE....

67597 ADHESIVE POLAQUA 127-07
MANF: ADM TRONICS
....NO TEST DATA AVAILABLE....

20265 ADHESIVE POLYAMIDE SL6 GID: ADARXX
MANF: W L GORE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00001.41	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005330 0

06204 ADHESIVE POLYAMIDE V40 GID: ABXXXX
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE....

65951 ADHESIVE POLYCO 117-55
MANF: BORDEN
....NO TEST DATA AVAILABLE....

65952 ADHESIVE POLYCO 2113
MANF: BORDEN
....NO TEST DATA AVAILABLE....

65953 ADHESIVE POLYCO 2116
MANF: BORDEN
....NO TEST DATA AVAILABLE....

65954 ADHESIVE POLYCO 2123
MANF: BORDEN
....NO TEST DATA AVAILABLE....

65955 ADHESIVE POLYCO 2142
MANF: BORDEN
....NO TEST DATA AVAILABLE....

65956 ADHESIVE POLYCO 2149
MANF: BORDEN
....NO TEST DATA AVAILABLE....

65957 ADHESIVE POLYCO 2150
MANF: BORDEN
....NO TEST DATA AVAILABLE....

65958 ADHESIVE POLYCO 2186
MANF: BORDEN
....NO TEST DATA AVAILABLE....

65959 ADHESIVE POLYCO 571
MANF: BORDEN
....NO TEST DATA AVAILABLE....

06443 ADHESIVE POLYESTER ETC1 GID: ABCBXX
MANF: ELECTRO TECH
....NO TEST DATA AVAILABLE....

06622 ADHESIVE POLYFREEZE P146 EPOXY GID: ABBGXX
MANF: POLY-FREEZE

SPEC: MC476-0028 MMS2518

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	020.9	014.7	0.034		00.00	00.00	NONE	No test data	No test data						
X	1	020.9	014.7	0.034			11.00	MOD								

20251 ADHESIVE POLYOLEFIN S1024 GID: ABXXXX
....NO TEST DATA AVAILABLE....

66895 ADHESIVE POLYPLUS 165
MANF: I W INDUSTRIES INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005331 2

66419 ADHESIVE POLYSEAMSEAL 2002 CLEAR CAULK
MANF: E B INDUSTRIES
....NO TEST DATA AVAILABLE....

66418 ADHESIVE POLYSEAMSEAL ALL PURPOSE CAULK
MANF: E B INDUSTRIES
....NO TEST DATA AVAILABLE....

05694 ADHESIVE POLYSULFIDE PR14600 GID: BADLXX
MANF: PROD RESEARCH & CHEM SPEC: MIL-S-8802CA

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	6.12	.67	.00		No test data		

81709 ADHESIVE POLYTECH 4000
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81710 ADHESIVE POLYTECH 4020
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81711 ADHESIVE POLYTECH 4140
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81712 ADHESIVE POLYTECH 4150
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

05829 ADHESIVE POLYURETHANE C7-4247 GID: ABCQXX
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	9.0E-7	.78	.03			V	00009.99	

60263 ADHESIVE POLYURETHANE MODIFIED STMM476 GID: ABCQXX
....NO TEST DATA AVAILABLE....

67125 ADHESIVE POWERBOND 919
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67126 ADHESIVE POWERBOND 920
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67127 ADHESIVE POWERBOND 922
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67134 ADHESIVE PR1221 CLASS A
MANF: PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	020.9	014.7	0.015	0.004		12.00	NONE	No test data		No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005332 4

67135 ADHESIVE PR1321 CLASS A
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82285 ADHESIVE PR1403G A-1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82286 ADHESIVE PR1403G A-2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82287 ADHESIVE PR1403G B-1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82288 ADHESIVE PR1403G B-2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82289 ADHESIVE PR1422A1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82290 ADHESIVE PR1422A2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82291 ADHESIVE PR1422B1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82292 ADHESIVE PR1422B2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82293 ADHESIVE PR1422G B1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82294 ADHESIVE PR1422G B2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82282 ADHESIVE PR1425B1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82283 ADHESIVE PR1425B2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82295 ADHESIVE PR1426
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005333 6

Information Handling Services, 2000

82297 ADHESIVE PR1431G T2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82298 ADHESIVE PR1431G T3
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82299 ADHESIVE PR1431G T4
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82296 ADHESIVE PR1431G TI
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82300 ADHESIVE PR1435
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82301 ADHESIVE PR1435G
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82302 ADHESIVE PR1436G A1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82303 ADHESIVE PR1436G A2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82304 ADHESIVE PR1436G B2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82305 ADHESIVE PR1436G B4
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82306 ADHESIVE PR1436G SPRAYABLE
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82307 ADHESIVE PR1440A1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82308 ADHESIVE PR1440A2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82309 ADHESIVE PR1440B1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005334 8

82310 ADHESIVE PR1440B2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82311 ADHESIVE PR1440C2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82312 ADHESIVE PR1440C20
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

62345 ADHESIVE PR1546L GID: ABXXXX
MANF: PROD RESEARCH & CHEM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.65	.04	.44	3H-70F- 60H-176F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60272 ADHESIVE PR1590 GID: ABXXXX
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

67146 ADHESIVE PR1710
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

03280 ADHESIVE PR1710-1711 VITON GID: ABDEXX
MANF: PROD RESEARCH & CHEM SPEC: MB0130-106

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.007	0.003		01.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.66	.05	.00	16H-70F- 2H-250F-

ODOR

RT	RT WEIGHT	CURE
A	B 00022.78	168H-70F-

TOXICITY

82284 ADHESIVE PR1725B2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

61542 ADHESIVE PR175082 POLYSULFIDE GID: BADLXX
MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.068	0.003		01.10	NONE
C	1	023.8	014.5	0.068	0.003	00.17	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
X	V 00249.99	168H-70F- 24H-150F-

TOXICITY

82314 ADHESIVE PR1750A-2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005335 T

82313 ADHESIVE PR1750A1/2
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82315 ADHESIVE PR1755
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

67139 ADHESIVE PR2701
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

67140 ADHESIVE PR2702
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

67141 ADHESIVE PR2751
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

67142 ADHESIVE PR2752
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

67137 ADHESIVE PR380
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

67138 ADHESIVE PR383
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82316 ADHESIVE PR702
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82317 ADHESIVE PR703
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82318 ADHESIVE PR810
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

82319 ADHESIVE PR812
MANF: PROD RESEARCH & CHEM

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7	0.063	0.02		07.00	NONE	No test data		No test data							

67143 ADHESIVE PR927
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

67144 ADHESIVE PR938
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005336 1

67145 ADHESIVE PR957
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

62109 ADHESIVE PRESSURE SENSITIVE GID: AFXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.2E-7	2.75	.04		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

85506 ADHESIVE PRESSURE SENSITIVE
MANF: MORTON CHEMICAL DIVISION, MTI

SPEC: MIL-T-81533
STW5-3479

STW 3431

....NO TEST DATA AVAILABLE....

69847 ADHESIVE PRIMER CHEMLOK 205 RUBBER-TO-METAL GID: AUXXXX
MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
X	5.69	24H-70F-

TOXICITY

05108 ADHESIVE PROSEAL 828 EPOXY GID: ABBGXX
MANF: COAST PROSEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.026		00.00	00.00	NONE
A	1	023.8	014.5	0.026			03.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.60	.02	.00	1H-351F-

ODOR

RT	RT WEIGHT	CURE
A	A 00039.90	

TOXICITY

05109 ADHESIVE PROSEAL 829 EPOXY GID: ABBGXX
MANF: COAST PROSEAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.44	.02	.00	1H-351F-

ODOR

RT	RT WEIGHT	CURE
A	B 00037.16	1.5H-225F-

TOXICITY

06416 ADHESIVE PROSEAL 840 EPOXY GID: ABBGXX
MANF: COAST PROSEAL
....NO TEST DATA AVAILABLE....

20661 ADHESIVE PUREBOND P658RC GID: ABXXXX
MANF: PURE CARBON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	033.0	014.3	0.120		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.2E-6	1.38	.03		

ODOR

RT	RT WEIGHT	CURE
V	00020.30	

TOXICITY

66413 ADHESIVE PYRALUX WA/A
MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.15	.01	.22	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005337 3

65808 ADHESIVE PYROBOND 566
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

65809 ADHESIVE PYROPUTTY 600
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

65669 ADHESIVE QUANTUM 701
MANF: ALLIED RESIN CORP
....NO TEST DATA AVAILABLE....

65670 ADHESIVE QUANTUM 702
MANF: ALLIED RESIN CORP
....NO TEST DATA AVAILABLE....

65671 ADHESIVE QUANTUM 703
MANF: ALLIED RESIN CORP
....NO TEST DATA AVAILABLE....

67128 ADHESIVE QUICKBOND 513
MANF: COLORITE PLASTICS CO
PERMABOND
....NO TEST DATA AVAILABLE....

67129 ADHESIVE QUICKBOND 523
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67130 ADHESIVE QUICKBOND 610
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67131 ADHESIVE QUICKBOND 612
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

84998 ADHESIVE QUICKBOND 614/610
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67132 ADHESIVE QUICKBOND 650
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

67170 ADHESIVE R1003
MANF: RTE CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	4.18	1.10	.00		No test data		

67171 ADHESIVE R1007
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

67172 ADHESIVE R3500
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005338 5

05945 ADHESIVE R393 GID: ABBGXX
MANF: APPLIED PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.007	0.003	00.00	00.00	NONE
X	1	023.8	014.5	0.007	0.003		06.10	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00016.71	3H-200F-

67151 ADHESIVE R81005
MANF: RAYMARK INDUSTRIAL DIVISION
....NO TEST DATA AVAILABLE....

67152 ADHESIVE R81007
MANF: RAYMARK INDUSTRIAL DIVISION
....NO TEST DATA AVAILABLE....

67153 ADHESIVE R81012
MANF: RAYMARK INDUSTRIAL DIVISION
....NO TEST DATA AVAILABLE....

67154 ADHESIVE R81816
MANF: RAYMARK INDUSTRIAL DIVISION
....NO TEST DATA AVAILABLE....

67155 ADHESIVE R82007
MANF: RAYMARK INDUSTRIAL DIVISION
....NO TEST DATA AVAILABLE....

67156 ADHESIVE R82016
MANF: RAYMARK INDUSTRIAL DIVISION
....NO TEST DATA AVAILABLE....

67157 ADHESIVE R84017
MANF: RAYMARK INDUSTRIAL DIVISION
....NO TEST DATA AVAILABLE....

67158 ADHESIVE R84025
MANF: RAYMARK INDUSTRIAL DIVISION
....NO TEST DATA AVAILABLE....

67159 ADHESIVE R84048
MANF: RAYMARK INDUSTRIAL DIVISION
....NO TEST DATA AVAILABLE....

67160 ADHESIVE R84067
MANF: RAYMARK INDUSTRIAL DIVISION
....NO TEST DATA AVAILABLE....

67161 ADHESIVE R85013
MANF: RAYMARK INDUSTRIAL DIVISION
....NO TEST DATA AVAILABLE....

20130 ADHESIVE R92039/H23490 EPOXY AB/BG GID: ABBGXX
MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005339 7

20130 ADHESIVE B92039/H23490 EPOXY AB/BG (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.008	0.003		06.30	SMALL
I	1	025.9	014.3	0.018	0.003	00.64	12.00 T	NONE
X	1	100.0	016.5	0.018	0.003	00.87	12.00 T	MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-7	.31	.01		24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00049.06	24H-70F- 24H-150F-

84074 ADHESIVE RAILSAFE ENGINE SEAL 12336
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

67012 ADHESIVE RAPIDSET 51QST
MANF: MERECO
....NO TEST DATA AVAILABLE....

67013 ADHESIVE RAPIDSET 52SST
MANF: MERECO
....NO TEST DATA AVAILABLE....

67014 ADHESIVE RAPIDSET 53HRT
MANF: MERECO
....NO TEST DATA AVAILABLE....

61466 ADHESIVE RAPIDSET BLUE EPOXY GID: ABBGXX
MANF: ARAN DEE ASSOCIATES SPEC: MIL-A-46050

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.001	0.003		01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00000.27	24H-70F- 24H-150F-

67041 ADHESIVE RAPIDSET SERIES 2
MANF: MERECO
....NO TEST DATA AVAILABLE....

67042 ADHESIVE RAPIDSET SERIES 3
MANF: MERECO
....NO TEST DATA AVAILABLE....

67040 ADHESIVE RAPIDSET SERIES VISCA CYANOACRYLATE ADH
MANF: MERECO
....NO TEST DATA AVAILABLE....

67556 ADHESIVE RAYBOND R85014
MANF: RAYMARK INDUSTRIAL DIVISION
....NO TEST DATA AVAILABLE....

67557 ADHESIVE RAYBOND R86009
MANF: RAYMARK INDUSTRIAL DIVISION
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005340 3

67558 ADHESIVE RAYBOND R86025
MANF: RAYMARK INDUSTRIAL DIVISION
....NO TEST DATA AVAILABLE....

62447 ADHESIVE RE2039/H3537 EPOXY GID: BABGXX
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.8E-6	.34	.01	.22	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

85423 ADHESIVE REDUX 410NA EPOXY
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

61299 ADHESIVE RELIABOND 382 EPOXY FILM GID: ACBGXX
MANF: RELIABLE MFG

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	11.09	.12	.00	1H-250F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05141 ADHESIVE RELIABOND 398 EPOXY FILM GID: ACBGXX
MANF: RELIABLE MFG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.018		00.06	09.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.17	.01	.00	

ODOR

RT	RT WEIGHT	CURE
A	K 00060.14	

TOXICITY

60523 ADHESIVE RELIABOND 7115 EPOXYFILM GID: ACBGXX
MANF: RELIABLE MFG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.004	0.003	00.84	11.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.96	.06		1H-250F-

ODOR

RT	RT WEIGHT	CURE
A	A 00017.43	

TOXICITY

06590 ADHESIVE RESIN POLYESTER 988 GID: ABBG
MANF: INTERCHEM CO
....NO TEST DATA AVAILABLE....

20297 ADHESIVE RESIWELD 4 EPOXY GID: ABBGXX
MANF: ROBERTSHAW

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.011	0.003		05.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.2E-7	1.36	.03		

ODOR

RT	RT WEIGHT	CURE
A	B 00022.61	168H-70F- 24H-150F-

TOXICITY

20387 ADHESIVE RESIWELD 7004 GID: BABLGS
MANF: H B FULLER
SPEC: ST32R155-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.015	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005341 5

20387 ADHESIVE RESIWELD 7004 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	023.8	014.5	0.015	0.003	00.15	12.00 T	SMALL
C	2	025.9	014.3	0.008	0.003		00.00	NONE
C	1	025.9	014.3	0.008	0.003	00.14	12.00 T	SMALL
C	2	025.9	014.3	0.011	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.011	0.003	00.33	12.00 T	SMALL

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.67	.12	.00	24H-77F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00022.57	24H-70F-25.9% OXYGEN 24H-150F-

20716 ADHESIVE RESIWELD 7004/5% CABOSIL GID: ABBGXX

MANF: H B FULLER

SPEC: ST32R155 ST32R15S
ST80C763 ST80C783

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.022	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.022	0.003	00.26	12.00 T	SMALL
I	1	030.0	009.0	0.022	0.003	00.21	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	2.38	.15		168H-70F- 3H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.56	168H-70F- 3H-150F-

81723 ADHESIVE RESIWELD FE0004
MANF: H B FULLER
....NO TEST DATA AVAILABLE....

81724 ADHESIVE RESIWELD FE0185
MANF: H B FULLER
....NO TEST DATA AVAILABLE....

81725 ADHESIVE RESIWELD FE1402
MANF: H B FULLER
....NO TEST DATA AVAILABLE....

81726 ADHESIVE RESIWELD FE5050
MANF: H B FULLER
....NO TEST DATA AVAILABLE....

81727 ADHESIVE RESIWELD FE6721
MANF: H B FULLER
....NO TEST DATA AVAILABLE....

80271 ADHESIVE RESIWELD FE7002 EPOXY GID: ABXXXX

MANF: H B FULLER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.20	.04	.08	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

81728 ADHESIVE RESIWELD FE7005
MANF: H B FULLER
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005342 7

67133 ADHESIVE RI2
MANF: PERMABOND
....NO TEST DATA AVAILABLE....

06099 ADHESIVE RMI380 EPOXY GID: ABBGXX
....NO TEST DATA AVAILABLE....

67676 ADHESIVE RTC EPOXY
MANF: WILLIAM T. BEAN MICRO ENGINEER
....NO TEST DATA AVAILABLE....

66714 ADHESIVE RTV 109
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

66715 ADHESIVE RTV 161
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

66716 ADHESIVE RTV 31
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81818 ADHESIVE RTV 41
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.06	.45	.00	8H-70F- 4H-122F-	No test data		

69605 ADHESIVE RTV 730/RTV 1200 PRIME COAT
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

69606 ADHESIVE RTV 732/RTV 1200 PRIME COAT
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

69611 ADHESIVE RTV 738
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

69610 ADHESIVE RTV 739
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

83115 ADHESIVE RTV T200
MANF: SWS SILICONES
....NO TEST DATA AVAILABLE....

83116 ADHESIVE RTV T56
MANF: SWS SILICONES
....NO TEST DATA AVAILABLE....

60304 ADHESIVE RUBBER NBR/MEK
MANF: THIOKOL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005343 9

Information Handling Services, 2000

66411 ADHESIVE RUBBER SILICONE DC280A
MANF: DOW CORNING

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.03	.44	.00	16H-230F-	No test data		

65672 ADHESIVE RUBBER SILICONE RTV 1473
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

65673 ADHESIVE RUBBER SILICONE RTV 157
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

65674 ADHESIVE RUBBER SILICONE RTV 158
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

66410 ADHESIVE RUBBER SILICONE RTV 92-076
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

06428 ADHESIVE RUBBER SSH/SS1 SILICONE GID: ABCKXX
....NO TEST DATA AVAILABLE....

61762 ADHESIVE RUBINATE M/VITEL PE307 GID: ABCBGS
MANF: GOODYEAR

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.002	0.003		02.70	NONE	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	8.4E-7	.45	.06		1.5H-250F-	A	B 00003.37	1.5H-250F-

67148 ADHESIVE S1006
MANF: RAYCHEM CORP
....NO TEST DATA AVAILABLE....

67149 ADHESIVE S1010
MANF: RAYCHEM CORP
....NO TEST DATA AVAILABLE....

60402 ADHESIVE S1017
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

67150 ADHESIVE S1125
MANF: RAYCHEM CORP
....NO TEST DATA AVAILABLE....

60118 ADHESIVE S2288 GID: ABXXXX
MANF: DOW CORNING SPEC: STW5-2803
....NO TEST DATA AVAILABLE....

66522 ADHESIVE S860
MANF: ETHERINGTON/U S PROLAM
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005344 0

05477 ADHESIVE SAUEREISEN #29 INORGANIC GID: ABXXXV

MANF: SAUEREISEN CEMENT CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.038			01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.23	.00	.00	24H-77F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06082 ADHESIVE SAUEREISEN #8 INORGANIC GID: ABXXXX

MANF: SAUEREISEN CEMENT CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.69	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65917 ADHESIVE SC12

MANF: BACON

....NO TEST DATA AVAILABLE....

81729 ADHESIVE SC2505

MANF: H B FULLER

....NO TEST DATA AVAILABLE....

67291 ADHESIVE SCOTCHCAST 208

MANF: 3M CO

....NO TEST DATA AVAILABLE....

67292 ADHESIVE SCOTCHCAST 210

MANF: 3M CO

....NO TEST DATA AVAILABLE....

67293 ADHESIVE SCOTCHCAST 215

MANF: 3M CO

....NO TEST DATA AVAILABLE....

67294 ADHESIVE SCOTCHCAST 216

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.64	.15	.00	.33H-248F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

67295 ADHESIVE SCOTCHCAST 226

MANF: 3M CO

....NO TEST DATA AVAILABLE....

67296 ADHESIVE SCOTCHCAST 237

MANF: 3M CO

....NO TEST DATA AVAILABLE....

67297 ADHESIVE SCOTCHCAST 241

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.89	.01	.00	.25H-140F- 16H-200F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

MSFC-HDBK-527 REV F 9999942 0005345 2

Information Handling Services, 2000

67298 ADHESIVE SCOTCHCAST 243
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.02	.03	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

67299 ADHESIVE SCOTCHCAST 250
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67300 ADHESIVE SCOTCHCAST 252
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67301 ADHESIVE SCOTCHCAST 253
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67302 ADHESIVE SCOTCHCAST 255
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67303 ADHESIVE SCOTCHCAST 260
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.52	.03	.00	.5H-284F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

67304 ADHESIVE SCOTCHCAST 262
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.03	.01	.71	.75H-302F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

67305 ADHESIVE SCOTCHCAST 263
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67306 ADHESIVE SCOTCHCAST 265
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67307 ADHESIVE SCOTCHCAST 270
MANF: 3M CO
....NO TEST DATA AVAILABLE....

20148 ADHESIVE SCOTCHCAST 280 A/B GID: ABBMXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.146			02.60	SMALL
X	2	030.0	010.0	0.090		00.01	01.50	MOD
X	1	030.0	010.0	0.090		00.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.48	.14	.00	2H-250F-
					24H-311F-

ODOR

RT	RT WEIGHT	CURE
X	00022.69	24H-149F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005346 4

67308 ADHESIVE SCOTCHCAST 282
MANF: 3M CO

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.49	.10	.00	16H-194F-	No test data		

67309 ADHESIVE SCOTCHCAST 3
MANF: 3M CO

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	4.62	.24	.00	4H-250F-	No test data		

67310 ADHESIVE SCOTCHCAST 5064
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67311 ADHESIVE SCOTCHCAST 5140
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67312 ADHESIVE SCOTCHCAST 5166
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67314 ADHESIVE SCOTCHCAST 5235
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67315 ADHESIVE SCOTCHCAST 5237
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67316 ADHESIVE SCOTCHCAST 5240
MANF: 3M CO

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	4.20	1.06	.00	3H-149F-	No test data		

67317 ADHESIVE SCOTCHCAST 5241
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67318 ADHESIVE SCOTCHCAST 5242
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67319 ADHESIVE SCOTCHCAST 5243
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67320 ADHESIVE SCOTCHCAST 5326
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67321 ADHESIVE SCOTCHCAST 9
MANF: 3M CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005347 6

60721 ADHESIVE SCOTCHGRIP 1099 VINYL GID: ABCUXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		01.80	SMALL
A	1	023.8	014.5	0.007	0.003		03.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.1E-7	6.11	.23		24H-160F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00006.10	24H-70F-
		24H-160F-

62243 ADHESIVE SCOTCHGRIP 1300 GID: ABXXXX

MANF: 3M CO SPEC: HS 1265

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.005	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.005	0.003	00.52	12.00 T	NONE
A	1	100.0	019.0	0.001	0.125	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	2.55	.20		168H-70F-
					24H-150F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00019.05	168H-70F-
		24H-150F-

67686 ADHESIVE SCOTCHGRIP 1357 NEUTRAL

MANF: 3M CO

....NO TEST DATA AVAILABLE....

05435 ADHESIVE SCOTCHGRIP 1711 GID: ABDBXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.006	0.003		02.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.4E-6	4.59	.63		168H-70F-
					24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00004.99	168H-70F-
		24H-150F-

60719 ADHESIVE SCOTCHGRIP 2126 GID: ABHBXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.3E-7	8.71	1.99		24H-160F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00003.58	24H-70F-
		24H-160F-

05438 ADHESIVE SCOTCHGRIP 2210 GID: ABBGXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.015	0.003		05.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.6E-6	1.81	.02		168H-70F-
					24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00003.65	168H-70F-
		24H-150F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005348 8

67696 ADHESIVE SCOTCHGRIP 2226 GREEN
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67339 ADHESIVE SCOTCHGRIP 4518
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67579 ADHESIVE SCOTCHGRIP 5034 NEUTRAL
MANF: 3M CO
....NO TEST DATA AVAILABLE....

61572 ADHESIVE SCOTCHGRIP 847 GID: ABBGXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.003		03.60	NONE
A	1	030.0	009.0	0.003	0.003		02.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.80	.57	.00	2H-200F- 24H-199F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00017.35	2H-200F-

67578 ADHESIVE SCOTCHGRIP 847H
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67577 ADHESIVE SCOTCHGRIP 847L
MANF: 3M CO
....NO TEST DATA AVAILABLE....

20566 ADHESIVE SCOTCHGRIP EC1300L GID: ABXXXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.003		05.20	NONE
B	1	033.0	014.3	0.003	0.003		08.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.03	1.19	7.46	1H-140F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.19	24H-70F- 24H-150F-

67289 ADHESIVE SCOTCHMELT E3861
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83653 ADHESIVE SCOTCHSEAL 1252
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83654 ADHESIVE SCOTCHSEAL 1279
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83651 ADHESIVE SCOTCHSEAL 1792
MANF: 3M CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005349 T

83655 ADHESIVE SCOTCHSEAL 1814
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83656 ADHESIVE SCOTCHSEAL 2084
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83657 ADHESIVE SCOTCHSEAL 2084H
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67290 ADHESIVE SCOTCHSEAL 5200
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83658 ADHESIVE SCOTCHSEAL 612
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83659 ADHESIVE SCOTCHSEAL 750
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83660 ADHESIVE SCOTCHSEAL 800
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83661 ADHESIVE SCOTCHSEAL 801 B/A
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83662 ADHESIVE SCOTCHWELD 111
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83663 ADHESIVE SCOTCHWELD 13
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67285 ADHESIVE SCOTCHWELD 1357L
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83664 ADHESIVE SCOTCHWELD 15
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67343 ADHESIVE SCOTCHWELD 1751L
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83665 ADHESIVE SCOTCHWELD 2214 HI DENSITY
MANF: 3M CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005350 6 ■

Information Handling Services, 2000

83666 ADHESIVE SCOTCHWELD 2214 NI FLEX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83667 ADHESIVE SCOTCHWELD 2214 NONMETALLIC
MANF: 3M CO
....NO TEST DATA AVAILABLE....

05498 ADHESIVE SCOTCHWELD 2214HT GID: ABBHXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.008	0.003	00.00	00.00	NONE
B	1	023.8	014.5	0.008	0.003		06.20	NONE
X	1	023.8	014.5	0.007	0.003		03.10	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	1.18	.11	.49	.67H-250F-
					.67H-250F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00014.71	

67286 ADHESIVE SCOTCHWELD 2262
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83668 ADHESIVE SCOTCHWELD 3501 B/A
MANF: 3M CO
....NO TEST DATA AVAILABLE....

05503 ADHESIVE SCOTCHWELD 3520 B/A GID: ABBGXX
MANF: 3M CO SPEC: MIL-A-8623

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.018	0.003		04.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	1.23	.06		72H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00057.55	72H-70F-

67282 ADHESIVE SCOTCHWELD 3532 B/A
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.66	.07	.00	24H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

83669 ADHESIVE SCOTCHWELD 3533 B/A
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67283 ADHESIVE SCOTCHWELD 3535 B/A
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83670 ADHESIVE SCOTCHWELD 3553 B/A
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83671 ADHESIVE SCOTCHWELD 4060
MANF: 3M CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005351 8

83672 ADHESIVE SCOTCHWELD 42
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67287 ADHESIVE SCOTCHWELD 4475
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67288 ADHESIVE SCOTCHWELD 4693
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67284 ADHESIVE SCOTCHWELD 776
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67329 ADHESIVE SCOTCHWELD AF163-205T
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67325 ADHESIVE SCOTCHWELD AF163-24
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67327 ADHESIVE SCOTCHWELD AF163-2K
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67328 ADHESIVE SCOTCHWELD AF163-2M
MANF: 3M CO

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.50	.30	.92	1H-302F-

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

80170 ADHESIVE SCOTCHWELD AF191 STRUCTURAL FILM GID: BPXXXX
MANF: 3M CO

FLAMMABILITY								
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.016		1.3	12.00	T LARGE

FSC	
RT	FLUID NAME
No test data	

OXYGEN COMP						
RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	01.12	0.201	00.62	1H-350F-12.4psia

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
	X 22.025	1H-350F-12.4psia

67332 ADHESIVE SCOTCHWELD EC1469
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67331 ADHESIVE SCOTCHWELD EC1614
MANF: 3M CO

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.03	.66	.00	1.5H-149F-

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

67330 ADHESIVE SCOTCHWELD EC1648
MANF: 3M CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005352 T

05259 ADHESIVE SCOTCHWELD EC1838 B/A GID: ABBGXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005	0.003		03.10	SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.41	.03	.00	24H-46F- 1H-248F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00017.37	24H-70F- .42H-250F-

05226 ADHESIVE SCOTCHWELD EC2214 EPOXY GID: ABFWXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002	0.003		03.20	NONE
I	1	023.8	014.5	0.057	0.003	00.11	12.00	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.4E-6	1.16	.12	.40	24H-150F- 3H-275F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70	0.078	0	20
Z	MECH	1500	72	74	0.078	02	02

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05066 ADHESIVE SCOTCHWELD EC2216 B/A GID: ABBGXX

MANF: 3M CO

SPEC: IP20025 MBO120-086
MDM3279 MIL-A-46864

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.021	0.002	00.60	12.00	T LARGE
A	1	020.9	014.5	0.002	0.003		02.20	SMALL
A	1	023.8	014.5	0.005	0.003		02.40	NONE
A	1	023.8	014.5	0.002	0.003		02.20	SMALL
A	1	023.8	014.5	0.011	0.003		02.30	NONE
X	2	025.9	014.3	0.016	0.003	00.00	00.00	NONE
X	1	025.9	014.3	0.016	0.003	00.16	12.00	T MOD
A	1	030.0	010.0	0.007	0.003		05.60	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.68	.00	.27	24H-46F- 24H-203F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00030.76	2H-200F- 24H-150F-

67589 ADHESIVE SCOTCHWELD EC3420

MANF: 3M CO

....NO TEST DATA AVAILABLE....

83673 ADHESIVE SCOTCHWELD EC3430

MANF: 3M CO

....NO TEST DATA AVAILABLE....

67590 ADHESIVE SCOTCHWELD EC3446

MANF: 3M CO

....NO TEST DATA AVAILABLE....

67591 ADHESIVE SCOTCHWELD EC3448

MANF: 3M CO

....NO TEST DATA AVAILABLE....

60515 ADHESIVE SCOTCHWELD EC588 GID: ABBGXX

MANF: 3M CO

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005353 1

60515 ADHESIVE SCOTCHWELD EC588 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.009	0.003		09.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.21	.54	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00022.26	168H-70F- 24H-150F-

67582 ADHESIVE SCOTCHWELD FILM AF10
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67585 ADHESIVE SCOTCHWELD FILM AF111
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67583 ADHESIVE SCOTCHWELD FILM AF13
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67586 ADHESIVE SCOTCHWELD FILM AF147
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.21	.01	.12	1H-350F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

67587 ADHESIVE SCOTCHWELD FILM AF202
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67584 ADHESIVE SCOTCHWELD FILM AF32
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67581 ADHESIVE SCOTCHWELD FILM AF6
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67588 ADHESIVE SCOTCHWELD IXA3430
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67326 ADHESIVE SCOTCHWELD IXA3448
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67592 ADHESIVE SCOTCHWELD IXA3537
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67593 ADHESIVE SCOTCHWELD IXA3538
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67594 ADHESIVE SCOTCHWELD IXA3580
MANF: 3M CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005354 3 ■

61483 ADHESIVE SCOTCHWELD XA3950 GID: BAXXXX
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	9.0E-6	2.13	.05	.68	2.5H-75F- 1H-250F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

20149 ADHESIVE SCOTT 101 GID: ABBGXX
MANF: SCOTT AVIATION
....NO TEST DATA AVAILABLE....

06539 ADHESIVE SE851/CA2 GID: ABBGXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.077			01.50	NONE
X	1	025.9	014.3	0.077			06.20	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	B	00019.67	SEE MFG

06538 ADHESIVE SE871/CA2 GID: ABBGXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.7	0.082			01.50	NONE
X	1	025.9	014.7	0.082		00.06	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	B	00020.42	SEE MFG

06600 ADHESIVE SE881/CA2 GID: ABXXXX
MANF: GENERAL ELECTRIC

SPEC: MC8296-09T2, MC8296-09T3, MC8296-09T4, MC8296-10T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.010	0.003	00.04	12.00 T	MOD
X	1	025.9	014.3	0.010	0.003	00.43	12.00 T	NONE
I	1	025.9	014.3	0.075		00.26	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	B	00020.43	SEE FLAM CURE

85348 ADHESIVE SEALUM FM100
MANF: CHEMSECO
....NO TEST DATA AVAILABLE....

85349 ADHESIVE SEALUM SM501
MANF: CHEMSECO
....NO TEST DATA AVAILABLE....

85350 ADHESIVE SEALUM SM506
MANF: CHEMSECO
....NO TEST DATA AVAILABLE....

85351 ADHESIVE SEALUM SM507
MANF: CHEMSECO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005355 5

85352 ADHESIVE SEALUM SM508
MANF: CHEMSECO
....NO TEST DATA AVAILABLE....

85353 ADHESIVE SEALUM SM509
MANF: CHEMSECO
....NO TEST DATA AVAILABLE....

85354 ADHESIVE SEALUM SM532
MANF: CHEMSECO
....NO TEST DATA AVAILABLE....

20720 ADHESIVE SH238 GID: ABXXXX
MANF: TESTWORTH LABS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002	0.003		02.50	NONE
C	2	025.9	014.3	0.004	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.004	0.003	00.34	12.00	T SMALL
A	1	033.0	014.3	0.002	0.003		05.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	9.0E-7	.64	.06		24H-70F- 168H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.03	24H-70F-

67173 ADHESIVE SHELDAHL AKC012
MANF: SHELDAHL
....NO TEST DATA AVAILABLE....

67179 ADHESIVE SHELDAHL L1662
MANF: SHELDAHL
....NO TEST DATA AVAILABLE....

67174 ADHESIVE SHELDAHL MKC021
MANF: SHELDAHL
....NO TEST DATA AVAILABLE....

67178 ADHESIVE SHELDAHL T100
MANF: SHELDAHL
....NO TEST DATA AVAILABLE....

67183 ADHESIVE SHELDAHL T1502
MANF: SHELDAHL
....NO TEST DATA AVAILABLE....

67180 ADHESIVE SHELDAHL T1633
MANF: SHELDAHL
....NO TEST DATA AVAILABLE....

67181 ADHESIVE SHELDAHL T1650
MANF: SHELDAHL
....NO TEST DATA AVAILABLE....

67176 ADHESIVE SHELDAHL T1694
MANF: SHELDAHL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005356 7

82648 ADHESIVE SHELDAHL T300
MANF: SHELDAHL
....NO TEST DATA AVAILABLE....

67175 ADHESIVE SHELDAHL T329
MANF: SHELDAHL
....NO TEST DATA AVAILABLE....

67182 ADHESIVE SHELDAHL T340
MANF: SHELDAHL
....NO TEST DATA AVAILABLE....

67177 ADHESIVE SHELDAHL T400
MANF: SHELDAHL
....NO TEST DATA AVAILABLE....

66722 ADHESIVE SHURSTIK 486
MANF: GIBSON-HOMANS CO
....NO TEST DATA AVAILABLE....

66875 ADHESIVE SICOMET 40
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66876 ADHESIVE SICOMET 50
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66877 ADHESIVE SICOMET 5019
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66878 ADHESIVE SICOMET 5044
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66879 ADHESIVE SICOMET 65
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66880 ADHESIVE SICOMET 7000
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66881 ADHESIVE SICOMET 77
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66882 ADHESIVE SICOMET 7900
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66883 ADHESIVE SICOMET 8200
MANF: HENKEL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005357 9

Information Handling Services, 2000

66884 ADHESIVE SICOMET 8300
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66885 ADHESIVE SICOMET 8400
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66886 ADHESIVE SICOMET 85
MANF: HENKEL

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	7.90	.02	7.22	16H-158F-	No test data		

66887 ADHESIVE SICOMET 8546
MANF: HENKEL
....NO TEST DATA AVAILABLE....

66888 ADHESIVE SICOMET 99
MANF: HENKEL
....NO TEST DATA AVAILABLE....

82721 ADHESIVE SIKA 15LM
MANF: SIKA CHEMICAL
....NO TEST DATA AVAILABLE....

82722 ADHESIVE SIKAFLEX 1A
MANF: SIKA CHEMICAL
....NO TEST DATA AVAILABLE....

82723 ADHESIVE SIKAFLEX 2C NS/NL
MANF: SIKA CHEMICAL
....NO TEST DATA AVAILABLE....

67508 ADHESIVE SILAPRENE ADHESIVE/SEALANT
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67507 ADHESIVE SILAPRENE ALL WEATHER SEALANT
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67510 ADHESIVE SILAPRENE M6102
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67511 ADHESIVE SILAPRENE M6128
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67512 ADHESIVE SILAPRENE M6130
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67513 ADHESIVE SILAPRENE M6164
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005358 0

67514 ADHESIVE SILAPRENE M6234
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67515 ADHESIVE SILAPRENE M6249
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67516 ADHESIVE SILAPRENE M6272
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67517 ADHESIVE SILAPRENE M6287
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67518 ADHESIVE SILAPRENE M6302
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67519 ADHESIVE SILAPRENE M6303
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67520 ADHESIVE SILAPRENE M6306
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67521 ADHESIVE SILAPRENE M6310
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67522 ADHESIVE SILAPRENE M6314
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67523 ADHESIVE SILAPRENE M6321
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67524 ADHESIVE SILAPRENE M6347
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67525 ADHESIVE SILAPRENE M6378
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67526 ADHESIVE SILAPRENE M644D
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67527 ADHESIVE SILAPRENE M6531
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005359 2

Information Handling Services, 2000

67528 ADHESIVE SILAPRENE M6562
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67529 ADHESIVE SILAPRENE M6571
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67530 ADHESIVE SILAPRENE M6579
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67531 ADHESIVE SILAPRENE M6587
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

67509 ADHESIVE SILAPRENE MS038
MANF: UNIROYAL
....NO TEST DATA AVAILABLE....

66717 ADHESIVE SILGRIP PSA6573
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

20794 ADHESIVE SILGRIP SR529 SILICONE GID: ABCKXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.003		02.20	SMALL
A	1	030.0	009.0	0.003	0.003		02.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	X 00018.86	.33H-70F-

TOXICITY

06167 ADHESIVE SILGRIP SR573 SILICONE GID: ABCKXX
MANF: GENERAL ELECTRIC SPEC: ST31A095-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.3	0.006	0.003		03.40	NONE
A	1	023.8	014.3	0.006	0.003		03.40	NONE
A	1	024.5	014.3	0.006	0.003		03.40	NONE
A	1	025.9	014.3	0.006	0.003		03.40	NONE
A	1	025.9	014.3	0.009	0.003		02.20	NONE
A	1	030.0	014.3	0.006	0.003		03.80	NONE
A	1	033.0	014.3	0.006	0.003		03.80	NONE
X	1	100.0	020.2	0.007	0.003	01.62	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-7	1.10	.53		168H-70F- .02H-248F-

ODOR

RT	RT WEIGHT	CURE
A	B 00017.75	168H-70F- 720H-248F-

TOXICITY

60641 ADHESIVE SILGRIP SR6573 SILICONE GID: ABCKXX
MANF: GENERAL ELECTRIC SPEC: ST31A095-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	010.0	0.006	0.003		01.70	NONE
A	1	023.8	010.0	0.006	0.003		01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005360 9

60641 ADHESIVE SILGRIP SR6573 SILICONE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	010.0	0.006	0.003		01.70	NONE
A	1	025.9	010.0	0.006	0.003		01.70	NONE
A	1	030.0	010.0	0.006	0.003		01.70	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00016.15	24H-70F- 24H-150F-

06614 ADHESIVE SILGRIP SR6574 SILICONE GID: ABCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.005	0.003		01.70	NONE
A	1	030.0	009.0	0.005	0.003		02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.54	1.63	.00	24H-70F- 9H-150F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00020.54	SEE TVS CURE 1

06463 ADHESIVE SILICONE 9-5939-5 GID: ABCKXX

MANF: BENDIX

....NO TEST DATA AVAILABLE....

06331 ADHESIVE SILICONE BLK GL FIL GID: BACKIA

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.008	0.003		00.10	NONE
C	1	020.9	014.7	0.008	0.003	00.19	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.5E-6	.93	.26	.03	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

06365 ADHESIVE SILICONE DA4 GID: HBCKXX

MANF: WAHL INSTRUMENT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.010	0.003		02.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.3E-6	.83	.10	.01	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00022.74	

65441 ADHESIVE SILICONE DC999 GID: DPCKXX

MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.0E-6	.80	.02	.03	72H-76F- 72H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05948 ADHESIVE SILICONE G661 GID: ABCKXX

....NO TEST DATA AVAILABLE....

10277 ADHESIVE SILICONE GX6300 GID: ABCKXX

MANF: MARTIN MARIETTA

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005361 0

65442 ADHESIVE SILICONE SILITE 17150 GID: ABCKXX
MANF: DEVON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.84	.01	.07	SEE TEST REPORT

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

66258 ADHESIVE SILITE RTV HI-TEMP SILICONE
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66259 ADHESIVE SILITE RTV SILICONE
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

67420 ADHESIVE SILVER BOND TYPE 40
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67421 ADHESIVE SILVER BOND TYPE 50
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67422 ADHESIVE SILVER BOND TYPE 60
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67423 ADHESIVE SILVER EPOXY PASTE TYPE 1 AND 2
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

62251 ADHESIVE SILVER SILICONE GID: ABMRDP
MANF: TECHNICAL WIRE PROD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.014	0.010	00.00	00.00	NONE
A	1	030.0	014.3	0.012	0.010	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	X 00021.70	168H-70F-

60608 ADHESIVE SILVERBOND CONDUCTIVE GID: ABCKXX
MANF: TRANSENE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	2.03	.52	.08	2.5H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

61632 ADHESIVE SK43 SILICONE GID: ABCKXX
....NO TEST DATA AVAILABLE....

05844 ADHESIVE SM8103 SILICONE GID: ABCKXX
MANF: ITT CANNON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.3	0.004	0.003		01.20	SMALL
A	1	023.8	014.3	0.004	0.003		01.20	SMALL
A	1	024.5	014.3	0.004	0.003		01.20	SMALL
A	1	025.9	014.3	0.004	0.003		01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005362 2

05844 ADHESIVE SM8103 SILICONE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.4	0.004	0.003		01.40	SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.28	.14	.02	1H-433F-

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.73	1H-392F-

67424 ADHESIVE SMA100
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67425 ADHESIVE SMA1600
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67426 ADHESIVE SMA200
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67427 ADHESIVE SMA300
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67428 ADHESIVE SMA400
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67429 ADHESIVE SMA500
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67430 ADHESIVE SMA600
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67187 ADHESIVE SOLUBOND 1119
MANF: SOLUOL CHEMICAL CO
....NO TEST DATA AVAILABLE....

64065 ADHESIVE SOLUBOND 1121 GID: ABXXXX
MANF: SOLUOL CHEMICAL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.010	0.003	00.60	12.00	T MOD
X	1	030.0	010.0	0.010	0.003	01.40	12.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.2E-6	.68	.02	.51	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00019.74	

67188 ADHESIVE SOLUBOND 1122
MANF: SOLUOL CHEMICAL CO
....NO TEST DATA AVAILABLE....

67189 ADHESIVE SOLUBOND 1168
MANF: SOLUOL CHEMICAL CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005363 4

67185 ADHESIVE SOLUBOND 1173
MANF: SOLUOL CHEMICAL CO
....NO TEST DATA AVAILABLE....

67186 ADHESIVE SOLUBOND 1177
MANF: SOLUOL CHEMICAL CO
....NO TEST DATA AVAILABLE....

67562 ADHESIVE SOUNDSEAL ACOUSTICAL #909
MANF: 3M CO
....NO TEST DATA AVAILABLE....

66936 ADHESIVE SPEEDBONDER 324
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

62173 ADHESIVE SPEEDBONDER 324/CA707 GID: ABXXXX
MANF: LOCTITE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.00	.28	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

66937 ADHESIVE SPEEDBONDER 325
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

66938 ADHESIVE SPEEDBONDER 326
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

62543 ADHESIVE SPRAY 74 GID: ABXXXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.006	0.003		00.30	NONE
X	1	025.9	014.3	0.006	0.003		12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	V 00011.72	

TOXICITY

61797 ADHESIVE SPRAY 76 GID: ABXXXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.007	0.003	00.67	09.50	NONE
B	1	023.8	014.5	0.006	0.003	00.63	08.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.8E-7	8.88	4.36		24H-160F-0psia1E-1

ODOR

RT	RT WEIGHT	CURE
A	X 00006.09	24H-70F-

TOXICITY

60190 ADHESIVE SR529/SRC18 GID: ABXXXX
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	10.11	.49	.00	4H-190F-SEE REPT/4H-190F

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

MSFC-HDBK-527 REV F 9999942 0005364 6

Information Handling Services, 2000

05620 ADHESIVE STABOND C136 NITRILE GID: ABBGXX

MANF: STABOND CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.010	0.003		04.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

05741 ADHESIVE STABOND N125 NEOPRENE GID: ABDBXX

MANF: STABOND CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.004	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.004	0.003		01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00006.35	24H-150F-

60168 ADHESIVE STABOND T161 GID: ABXXXX

MANF: STABOND CORP SPEC: MMM-A-121

....NO TEST DATA AVAILABLE....

05525 ADHESIVE STABOND T190 NEOPRENE GID: ABDBXX

MANF: STABOND CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.007	0.003		02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	9.0E-7	4.25	.11		1H-70F- 24H-150F-

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE
B	00006.69	1H-70F- 24H-150F-

64334 ADHESIVE STANPAT GID: FXXXXX

MANF: STANPAT PROD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00027.50	

67638 ADHESIVE STONEPOXY KIT #6-2

MANF: CONAP

....NO TEST DATA AVAILABLE....

60361 ADHESIVE STRUCOL R1610 GID: ABXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.98	.00	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

60362 ADHESIVE STRUCOL R1612 GID: ABXXXX

....NO TEST DATA AVAILABLE....

85427 ADHESIVE STW53215 PRIMER WITH A187 XYLENE COUPLING AGENT GID: ABXXXX

MANF: THIOKOL/UNION CARBIDE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	.0005	0.003	00.03	01.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

06442 ADHESIVE STYCAST 2662/C14

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005365 8

05928 ADHESIVE STYCAST 2741/C15 GID: BABGXX
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	8.27	.55	.00	2H-149F-	No test data		

06130 ADHESIVE STYCAST 3020 GID: ABBGXX
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.04	.05	.00	SEE TEST REPORT	No test data		

67322 ADHESIVE SUPER 77 SPRAY
MANF: 3M CO

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	12.18	.41	.00	24H-77F-	No test data		

84075 ADHESIVE SUPERBONDER 409
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

66940 ADHESIVE SUPERBONDER 414
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

66939 ADHESIVE SUPERBONDER 415
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

66941 ADHESIVE SUPERBONDER 420
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

66942 ADHESIVE SUPERBONDER 422
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

66943 ADHESIVE SUPERBONDER 430
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

20704 ADHESIVE SUPERBONDER 496 ACRYLIC GID: ABAKXX
MANF: LOCTITE CORP SPEC: MIL-A-46050

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	43.66	.02		12H-70F-	A	V 00007.79	24H-70F-

67552 ADHESIVE SUPERBONDER 498
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

81087 ADHESIVE SUPERBONDER 499
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005366 T

81237 ADHESIVE SUPREME 10
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81240 ADHESIVE SUPREME 10G
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81242 ADHESIVE SUPREME 10HT
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81244 ADHESIVE SUPREME 10HT N
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81245 ADHESIVE SUPREME 10HT NHP
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81238 ADHESIVE SUPREME 10S1
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81247 ADHESIVE SUPREME 10TI
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81249 ADHESIVE SUPREME 11
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81251 ADHESIVE SUPREME 11HT
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81252 ADHESIVE SUPREME 3HT
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

81253 ADHESIVE SUPREME 3T
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

67197 ADHESIVE SWS931
MANF: STAUFFER CHEMICAL
....NO TEST DATA AVAILABLE....

67196 ADHESIVE SWS990
MANF: STAUFFER CHEMICAL
....NO TEST DATA AVAILABLE....

67198 ADHESIVE SWST60
MANF: STAUFFER CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005367 1

Information Handling Services, 2000

06328 ADHESIVE SYLGARD 187 GID: ABCKXX
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	2.54	1.20	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06081 ADHESIVE SYS-SILICA (INORGANIC) GID: ABXXXX
MANF: SPEC: MA0106-379
....NO TEST DATA AVAILABLE....

67191 ADHESIVE T165
MANF: STABOND CORP
....NO TEST DATA AVAILABLE....

67190 ADHESIVE T440
MANF: STABOND CORP
....NO TEST DATA AVAILABLE....

80130 ADHESIVE TAKPAK GID: ABXXXX
MANF: LOCTITE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	024.5	014.5	0.040	0.013		01.50	NONE
C	1	024.5	014.5	0.040	0.013	1.0	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
X	22.797	

TOXICITY

66267 ADHESIVE TANKITE 2
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66603 ADHESIVE TCR12-100
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

66604 ADHESIVE TCR12-15
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

66602 ADHESIVE TCR2773
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

66605 ADHESIVE TCR2820
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

05530 ADHESIVE TECHKIT TS118-6 GID: ABBGXX
MANF: TECKNIT
....NO TEST DATA AVAILABLE....

83151 ADHESIVE TECKBOND 72-00118
....NO TEST DATA AVAILABLE....

83152 ADHESIVE TECKBOND 72-00119
MANF: TECKNIT
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005368 3

83153 ADHESIVE TECKBOND 72-00125
MANF: TECKNIT
....NO TEST DATA AVAILABLE....

66414 ADHESIVE TERATHANE POLYETHER GLOCOLS
MANF: DUPONT
....NO TEST DATA AVAILABLE....

61017 ADHESIVE TERLAN 1580 POLYIMIDE GID: ADCDXX
MANF: TERRELL CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002	0.003		04.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00011.02	

06559 ADHESIVE THERMAL 4952 EPOXY GID: ABBGXX
MANF: THERMALLOY
....NO TEST DATA AVAILABLE....

06064 ADHESIVE THERMAL CONDUCT SILICONE
MANF: BACON
SPEC: AB0120-068CZRVC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.007	0.003		00.50	NONE
A	1	025.9	014.3	0.010	0.003		01.00	SMALL
A	1	030.0	009.0	0.007	0.003		00.60	NONE
A	1	030.0	009.0	0.009	0.003		00.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	.48	.14		1H-70F- 4H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.49	1H-70F- 4H-150F-

80234 ADHESIVE THERMAL CONDUCTIVE A140 FR R1 GID: ABXXXX
MANF: DENKI KAGAKU KOGYO CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.007	0.003		02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	21.575	24H-77F-

67206 ADHESIVE THERMALBOND
MANF: THERMALLOY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.81	.07	.00	168H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05981 ADHESIVE THERMASIL 1 MODIFIED GID: ABBGXX
MANF: TRANSENE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.011	0.003		01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.7E-6	.66	.36		4.5H-203F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00017.47	4.5H-203F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005369 5

06014 ADHESIVE THERMASIL T2/CS GID: AVCKXX
MANF: TRANSENE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.006	0.003		00.50	NONE
A	1	023.8	014.5	0.045	0.003		01.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.0E-7	.58	.17		15H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00136.22	15H-70F-

60979 ADHESIVE THERMOFOAM 3008 GID: ABXXXX
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.2E-6	.95	.01	.72	.5H-335F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

66360 ADHESIVE THERMOFOAM 3028
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66361 ADHESIVE THERMOFOAM 3050
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66362 ADHESIVE THERMOFOAM 3056
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

66003 ADHESIVE THERMOGRIP 6363
MANF: BOSTIK FINCH
....NO TEST DATA AVAILABLE....

62351 ADHESIVE THERMOGRIP 6363-15 GID: ABXXXX
MANF: BOSTIK FINCH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.460			02.40	SMALL
X	1	033.0	014.3	0.460		00.10	04.80	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00019.97	

62350 ADHESIVE THERMOGRIP 6368-15 GID: ABXXXX
MANF: BOSTIK FINCH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.460		00.05	07.70	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.98	

83628 ADHESIVE THERMOSET 100
MANF: THERMOSET PLASTICS
....NO TEST DATA AVAILABLE....

83629 ADHESIVE THERMOSET 101
MANF: THERMOSET PLASTICS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005370 1

83630 ADHESIVE THERMOSET 103
MANF: THERMOSET PLASTICS
....NO TEST DATA AVAILABLE....

83631 ADHESIVE THERMOSET 104
MANF: THERMOSET PLASTICS
....NO TEST DATA AVAILABLE....

83632 ADHESIVE THERMOSET 125
MANF: THERMOSET PLASTICS.
....NO TEST DATA AVAILABLE....

83633 ADHESIVE THERMOSET 267
MANF: THERMOSET PLASTICS
....NO TEST DATA AVAILABLE....

83634 ADHESIVE THERMOSET DC232
MANF: THERMOSET PLASTICS
....NO TEST DATA AVAILABLE....

83635 ADHESIVE THERMOSET DC80
MANF: THERMOSET PLASTICS
....NO TEST DATA AVAILABLE....

83636 ADHESIVE THERMOSET EP233
MANF: THERMOSET PLASTICS
....NO TEST DATA AVAILABLE....

83637 ADHESIVE THERMOSET EP280
MANF: THERMOSET PLASTICS
....NO TEST DATA AVAILABLE....

83638 ADHESIVE THERMOSET EP433
MANF: THERMOSET PLASTICS
....NO TEST DATA AVAILABLE....

83639 ADHESIVE THERMOSET EP539
MANF: THERMOSET PLASTICS
....NO TEST DATA AVAILABLE....

83640 ADHESIVE THERMOSET EP548
MANF: THERMOSET PLASTICS
....NO TEST DATA AVAILABLE....

83641 ADHESIVE THERMOSET EP598
MANF: THERMOSET PLASTICS
....NO TEST DATA AVAILABLE....

66199 ADHESIVE THIXON 300/301
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66200 ADHESIVE THIXON 305
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005371 3

Information Handling Services, 2000

66201 ADHESIVE THIXON 409
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66202 ADHESIVE THIXON 416
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66203 ADHESIVE THIXON 508
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66204 ADHESIVE THIXON 511T
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66205 ADHESIVE THIXON 711
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66206 ADHESIVE THIXON 752
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66207 ADHESIVE THIXON 803-1
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

05850 ADHESIVE THIXON 806 (AP1442) GID: ABXXXX
MANF: DAYTON PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.0	014.7	0.003	0.003		02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.8E-7	8.50	.12		24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00005.09	24H-70F-

06400 ADHESIVE THIXON 807 (AP1559) NEOPRENE GID: ABXXXX
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66208 ADHESIVE THIXON 814-1
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66209 ADHESIVE THIXON 925
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66210 ADHESIVE THIXON 926
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66211 ADHESIVE THIXON 927
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005372 5

66212 ADHESIVE THIXON 936
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66213 ADHESIVE THIXON 942
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66214 ADHESIVE THIXON 943
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66215 ADHESIVE THIXON 954
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66216 ADHESIVE THIXON AP3395
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66217 ADHESIVE THIXON GPO
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66218 ADHESIVE THIXON OSN2
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66219 ADHESIVE THIXON P10
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66220 ADHESIVE THIXON P6-1
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

66221 ADHESIVE THIXON P7
MANF: DAYTON PRODUCTS
....NO TEST DATA AVAILABLE....

67553 ADHESIVE THREADLOCKER 222
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

67554 ADHESIVE THREADLOCKER 242
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

67555 ADHESIVE THREADLOCKER 290
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

63945 ADHESIVE THREE SEALING COMPOUND
MANF: THREEBOND OF AMERICA

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	030.0	010.0	0.001	0.003	01.89	11.90	NONE	No test data		No test data							

MSFC-HDBK-527 REV F ■ 9999942 0005373 7 ■

Information Handling Services, 2000

63945 ADHESIVE THREE SEALING COMPOUND (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00001.40	

TOXICITY

66627 ADHESIVE TITEBOND 35
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66628 ADHESIVE TITEBOND 50
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66629 ADHESIVE TITEBOND 55T
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66630 ADHESIVE TITEBOND DOWEL DRIVER
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66631 ADHESIVE TITEBOND IMPERIAL
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66632 ADHESIVE TITEBOND REGULAR
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66633 ADHESIVE TITEBOND SUPREME
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66634 ADHESIVE TOPSPEED ASSEMBLY GLUE
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

67389 ADHESIVE TRABOND 2101
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67390 ADHESIVE TRABOND 2106
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67391 ADHESIVE TRABOND 2106T
MANF: TRA-CON INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.35	.08	.00	168H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

67392 ADHESIVE TRABOND 2111
MANF: TRA-CON INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.90	.08	.00	72H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005374 9

67393 ADHESIVE TRABOND 2113
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67394 ADHESIVE TRABOND 2114
MANF: TRA-CON INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.16	.62	.00	72H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

67395 ADHESIVE TRABOND 2115
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67396 ADHESIVE TRABOND 2122
MANF: TRA-CON INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.15	.05	.00	72H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

67397 ADHESIVE TRABOND 2123
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67398 ADHESIVE TRABOND 2124
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67399 ADHESIVE TRABOND 2125
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67370 ADHESIVE TRABOND 2126
MANF: TRA-CON INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.27	.31	.00	168H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

67371 ADHESIVE TRABOND 2129
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67372 ADHESIVE TRABOND 2130
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67373 ADHESIVE TRABOND 2132
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67374 ADHESIVE TRABOND 2133
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67375 ADHESIVE TRABOND 21350
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005375 0

67376 ADHESIVE TRABOND 2143D
MANF: TRA-CON INC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.95	.06	.00	72H-70F-	No test data		

67377 ADHESIVE TRABOND 2147
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67378 ADHESIVE TRABOND 2151
MANF: TRA-CON INC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.65	.02	.00	72H-70F-	No test data		

67379 ADHESIVE TRABOND 2161
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67380 ADHESIVE TRABOND 21620
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67381 ADHESIVE TRABOND 2165
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67382 ADHESIVE TRABOND 2190
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67383 ADHESIVE TRABOND 2202
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67384 ADHESIVE TRABOND 2203
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67385 ADHESIVE TRABOND 2208
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67386 ADHESIVE TRABOND 2211
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67387 ADHESIVE TRABOND 2212
MANF: TRA-CON INC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.06	.03	.00	SEE TEST REPORT	No test data		

67388 ADHESIVE TRABOND 2215
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005376 2

67368 ADHESIVE TRABOND 2225
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67366 ADHESIVE TRABOND 2230
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67365 ADHESIVE TRABOND 2248
MANF: TRA-CON INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.72	.01	.00	16H-70F- 2H-149F- 2H-194F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

67369 ADHESIVE TRABOND 2254
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

20053 ADHESIVE TRABOND BB2112 GID: ABBGXX
MANF: TRA-CON INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.009	0.003	00.00	00.00	NONE
B	1	023.8	014.5	0.009	0.003		10.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60858 ADHESIVE TRABOND BB2116 GID: ABBGXX
MANF: TRA-CON INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.109			00.50	NONE
X	1	020.9	014.7	0.109		00.14	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.01	.05	.00	24H-70F-

ODOR

RT	RT WEIGHT	CURE
A	B 00020.03	24H-70F-

TOXICITY

65374 ADHESIVE TRABOND F1130F117 GID: ABBGXX
MANF: TRA-CON INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	X 00003.17	

TOXICITY

67367 ADHESIVE TRABOND KSMA
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67364 ADHESIVE TRADUCT 2924
MANF: TRA-CON INC
....NO TEST DATA AVAILABLE....

67431 ADHESIVE TRANSEAL 1175T
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

67432 ADHESIVE TRANSENE PDA D500
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005377 4

67433 ADHESIVE TRANSENE PDA S500
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

66553 ADHESIVE TRUCAST 111M
MANF: FENWAL INC
....NO TEST DATA AVAILABLE....

62725 ADHESIVE TRUCAST 111M/901 EPOXY GID: ABBGXX
MANF: FENWAL INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.3	0.010	0.040	00.06	06.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.61	.02	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

81979 ADHESIVE TUFFBOND
MANF: GOODLOE INC
....NO TEST DATA AVAILABLE....

81980 ADHESIVE TUFFBOND QUIK SET
MANF: GOODLOE INC
....NO TEST DATA AVAILABLE....

20305 ADHESIVE TYGOBOND 50 GID: ABXXXX
MANF: NORTON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.001	0.003	00.00	00.00	NONE
A	1	100.0	020.2	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	500	72	120	0.001	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-7	26.76	13.73	.00	48H-70F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
B	00005.21	48H-70F-

05792 ADHESIVE TYPLY 3 GID: ABXXXX
MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	500		250	0.001	0	20
I	MECH	500	72	250	0.001	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.6E-6	4.20	.00		48H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00002.37	48H-70F- 24H-150F-

66954 ADHESIVE TYRITE 7500
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66968 ADHESIVE TYRITE 7602
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66955 ADHESIVE TYRITE URETHANE
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005378 6

67195 ADHESIVE U148
MANF: STABOND CORP
....NO TEST DATA AVAILABLE....

20620 ADHESIVE U500-25 EPOXY GID: BABGXX
MANF: STERLING DIV OF REICHHOLD CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.4E-7	.41	.08		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

60986 ADHESIVE UK8202/UK5400 GID: ABXXXX
MANF: HENKEL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.2E-6	1.03	.08	.49	168H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

81088 ADHESIVE ULTRAVIOLET 352
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

81090 ADHESIVE ULTRAVIOLET 353
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

81091 ADHESIVE ULTRAVIOLET 354
MANF: LOCTITE CORP
....NO TEST DATA AVAILABLE....

20573 ADHESIVE UNIROYAL 6100 GID: ABXXXX
MANF: UNIROYAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002	0.003		03.40	NONE
B	1	033.0	014.3	0.003	0.003		08.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.2E-6	9.09	4.13		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00009.60	24H-70F-
		24H-150F-

65739 ADHESIVE UNISET 108B
MANF: AMICON
....NO TEST DATA AVAILABLE....

65740 ADHESIVE UNISET 3663
MANF: AMICON
....NO TEST DATA AVAILABLE....

65741 ADHESIVE UNISET 927-10
MANF: AMICON
....NO TEST DATA AVAILABLE....

65742 ADHESIVE UNISET A304-6
MANF: AMICON
....NO TEST DATA AVAILABLE....

65743 ADHESIVE UNISET A312
MANF: AMICON
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005379 8

65744 ADHESIVE UNISET A316-34
MANF: AMICON
....NO TEST DATA AVAILABLE....

06060 ADHESIVE UNISET A316-4 EPOXY GID: ABBGXX
MANF: AMICON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.5	0.007	0.003		03.70	NONE
A	1	023.8	014.5	0.007	0.003		03.70	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.1E-6	1.21	.52		.25H-250F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	K 00019.57	

65405 ADHESIVE UNISET A359-4 EPOXY GID: ABBGXX
MANF: AMICON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.010	0.003		03.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.49	.10		.66H-250F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	K 00023.31	

65746 ADHESIVE UNISET A410-10
MANF: AMICON
....NO TEST DATA AVAILABLE....

60718 ADHESIVE UNISET A451 EPOXY GID: ABBGXX
MANF: AMICON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		00.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	B 00047.35	8H-210F-

61223 ADHESIVE UNISET D271 EPOXY GID: ABBGXX
MANF: AMICON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.013	0.003		00.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	B 00045.04	.33H-250F-

65747 ADHESIVE UNISET D272
MANF: AMICON
....NO TEST DATA AVAILABLE....

65748 ADHESIVE UNISET D275
MANF: AMICON
....NO TEST DATA AVAILABLE....

65749 ADHESIVE UNISET D275-5
MANF: AMICON
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005380 4

65750 ADHESIVE UNISET D276
MANF: AMICON
....NO TEST DATA AVAILABLE....

65751 ADHESIVE UNISET D778
MANF: AMICON
....NO TEST DATA AVAILABLE....

65752 ADHESIVE UNISET D969
MANF: AMICON
....NO TEST DATA AVAILABLE....

65753 ADHESIVE UNISET E131
MANF: AMICON
....NO TEST DATA AVAILABLE....

65754 ADHESIVE UNISET E151-3
MANF: AMICON
....NO TEST DATA AVAILABLE....

65755 ADHESIVE UNISET E154
MANF: AMICON
....NO TEST DATA AVAILABLE....

65756 ADHESIVE UNISET E565
MANF: AMICON
....NO TEST DATA AVAILABLE....

65757 ADHESIVE UNISET G500
MANF: AMICON
....NO TEST DATA AVAILABLE....

65758 ADHESIVE UNISET G508
MANF: AMICON
....NO TEST DATA AVAILABLE....

65759 ADHESIVE UNISET G508-1
MANF: AMICON
....NO TEST DATA AVAILABLE....

65760 ADHESIVE UNISET G582
MANF: AMICON
....NO TEST DATA AVAILABLE....

65761 ADHESIVE UNISET G583
MANF: AMICON
....NO TEST DATA AVAILABLE....

65762 ADHESIVE UNISET G757-1
MANF: AMICON
....NO TEST DATA AVAILABLE....

65763 ADHESIVE UNISET G804-3
MANF: AMICON
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005381 6

65764 ADHESIVE UNISET G843
MANF: AMICON
....NO TEST DATA AVAILABLE....

65765 ADHESIVE UNISET SE613
MANF: AMICON
....NO TEST DATA AVAILABLE....

65766 ADHESIVE UNISET SE615
MANF: AMICON
....NO TEST DATA AVAILABLE....

65767 ADHESIVE UNISET SE616
MANF: AMICON
....NO TEST DATA AVAILABLE....

65768 ADHESIVE UNISET SE617
MANF: AMICON
....NO TEST DATA AVAILABLE....

65769 ADHESIVE UNISET SE628
MANF: AMICON
....NO TEST DATA AVAILABLE....

65770 ADHESIVE UNISET SE629
MANF: AMICON
....NO TEST DATA AVAILABLE....

65771 ADHESIVE UNISET SE630
MANF: AMICON
....NO TEST DATA AVAILABLE....

65772 ADHESIVE UNISET SE906-21
MANF: AMICON
....NO TEST DATA AVAILABLE....

65773 ADHESIVE UNISET T1207
MANF: AMICON
....NO TEST DATA AVAILABLE....

65774 ADHESIVE UNISET T1316
MANF: AMICON
....NO TEST DATA AVAILABLE....

65775 ADHESIVE UNISET T219
MANF: AMICON
....NO TEST DATA AVAILABLE....

65776 ADHESIVE UNISET T4009
MANF: AMICON
....NO TEST DATA AVAILABLE....

61776 ADHESIVE UNISET T530 GID: ABBGXX
MANF: AMICON

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
A	1	023.8	014.5	0.012	0.003		03.80	NONE	No test data		No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005382 8

61776 ADHESIVE UNISET T530 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00053.01	1H-140F-

65777 ADHESIVE UNISET T597
MANF: AMICON
....NO TEST DATA AVAILABLE....

65778 ADHESIVE UNISET T661
MANF: AMICON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.24	.03	.00	25H-70F- 2H-149F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

65779 ADHESIVE UNISET T665
MANF: AMICON
....NO TEST DATA AVAILABLE....

65780 ADHESIVE UNISET T920-2
MANF: AMICON
....NO TEST DATA AVAILABLE....

65784 ADHESIVE UNISET X2551
MANF: AMICON
....NO TEST DATA AVAILABLE....

65781 ADHESIVE UNISET XT116-1 WITH B71
MANF: AMICON
....NO TEST DATA AVAILABLE....

65782 ADHESIVE UNISET XT1203-4 WITH
MANF: AMICON
....NO TEST DATA AVAILABLE....

65783 ADHESIVE UNISET XT2526
MANF: AMICON
....NO TEST DATA AVAILABLE....

65785 ADHESIVE UNISET XT4064-3 WITH B100
MANF: AMICON
....NO TEST DATA AVAILABLE....

65786 ADHESIVE UNISET XT5012
MANF: AMICON
....NO TEST DATA AVAILABLE....

65787 ADHESIVE UNISET XT5066
MANF: AMICON
....NO TEST DATA AVAILABLE....

69828 ADHESIVE UNITAK 136 GID: ABXXXX
MANF: IMPERIAL ADHESIVE & CHEM INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.002	0.003		02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005383 T

69828 ADHESIVE UNITAK 136 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	9.48	1.47	.25	168H-70F- 24H-150F-

ODOR

RT	RT	WEIGHT	CURE
A	B	12.94	1H-70F- 168H-70F- 24H-150F-

TOXICITY

20326 ADHESIVE UR1087 VINYL/URETHANE GID: ABCUCQ

MANF: UBS CHEM

SPEC: ST30A073-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		01.70	NONE
B	1	033.0	014.3	0.001	0.003		06.50	NONE

FSC

RT	FLUID NAME
No test data	

ST30A093

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.2E-7	1.80	.08		24H-70F- 24H-150F-

ODOR

RT	RT	WEIGHT	CURE
A	X	00000.92	24H-70F- 24H-150F-

TOXICITY

81730 ADHESIVE UR2139

MANF: H B FULLER

....NO TEST DATA AVAILABLE....

81731 ADHESIVE UR2170

MANF: H B FULLER

....NO TEST DATA AVAILABLE....

81732 ADHESIVE UR2183

MANF: H B FULLER

....NO TEST DATA AVAILABLE....

06273 ADHESIVE URALANE 5738 A/B POLYURETHANE GID: ABCQXX

MANF: FURANE
X1-1401/X1-1077

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.010	0.003		00.10	NONE
X	1	025.9	014.3	0.010	0.003	00.27	12.00 T	MOD
X	1	030.0	009.0	0.021	0.003		08.90	MOD
X	2	030.0	010.0	0.008	0.003	00.09	12.00 T	SMALL
X	1	030.0	010.0	0.009	0.003	0.6	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	10.71	6.11	.00	3H-200F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00021.31	20H-70F- 3H-150F-

TOXICITY

20207 ADHESIVE URALANE 5753 POLYURETHANE GID: BACQXX

MANF: FURANE
M & T CHEMICALS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.010	0.003	00.33	12.00 T	MOD
C	2	025.9	014.3	0.007	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.007	0.003	00.33	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.73	.03	.00	14H-100F- 24H-131F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00018.82	168H-70F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005384 1

66667 ADHESIVE URALANE 5754 A/B
MANF: FURANE
....NO TEST DATA AVAILABLE....

66668 ADHESIVE URALANE 5759 A/B
MANF: FURANE
....NO TEST DATA AVAILABLE....

66669 ADHESIVE URALANE 5764 A/B
MANF: FURANE
....NO TEST DATA AVAILABLE....

66680 ADHESIVE URALANE 5767
MANF: FURANE
....NO TEST DATA AVAILABLE....

66679 ADHESIVE URALANE 5768
MANF: FURANE
....NO TEST DATA AVAILABLE....

66678 ADHESIVE URALANE 8089
MANF: FURANE
....NO TEST DATA AVAILABLE....

61716 ADHESIVE URALANE 8267 POLYURETHANE GID: AKCQXX
MANF: FURANE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.011	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.011	0.003	00.00	00.00	NONE
A	1	024.5	014.5	0.130			02.40	SMALL
A	1	025.9	014.3	0.130			02.90	SMALL
A	1	030.0	010.0	0.130			03.70	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	14.14	.19	.00	168H-70F- 24H-150F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00007.61	24H-140F-0psiaVACUUM

66677 ADHESIVE URALANE 88800
MANF: FURANE
....NO TEST DATA AVAILABLE....

66676 ADHESIVE URALANE 88804
MANF: FURANE
....NO TEST DATA AVAILABLE....

61089 ADHESIVE URALITE 3124 POLYURETHANE RESIN GID: DLCQGS
MANF: HEXCEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.017	0.003	00.00	00.00	NONE
X	1	020.9	014.7	0.017	0.003		07.90	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.2E-6	1.64	.06	.39	1H-70F- 120H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005385 3

69851 ADHESIVE URALITE 3139 POLYURETHANE ORANGE
MANF: HEXCEL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	3.42	.07	.61	1H-150F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20327 ADHESIVE URETHANE 1246 A/B GID: ABCQXX
MANF: B F GOODRICH SPEC: ST32A094-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.004	0.003		03.00	NONE
C	1	033.0	014.3	0.004	0.003	00.66	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.76	.25		.5H-200F- 168H-70F-

ODOR

RT	RT WEIGHT	CURE
A	V 00002.04	.5H-200F- 168H-70F-

TOXICITY

61360 ADHESIVE URETHANE RP6401 GID: ABCQXX
MANF: REN PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.800		00.11	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	2.53	.02		24H-70F- 144H-70F-

ODOR

RT	RT WEIGHT	CURE
	B 00020.54	24H-70F- 144H-70F-

TOXICITY

66302 ADHESIVE UV153
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

66303 ADHESIVE UV210
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

66304 ADHESIVE UV300
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

66305 ADHESIVE UV307
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

66306 ADHESIVE UV448
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

66307 ADHESIVE UV450
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

81254 ADHESIVE UV5PSA
MANF: MASTER BOND
....NO TEST DATA AVAILABLE....

66308 ADHESIVE UV900
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005386 5

66309 ADHESIVE UV906
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

66310 ADHESIVE UV913
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

65788 ADHESIVE UV990-24-11
MANF: AMICON
....NO TEST DATA AVAILABLE....

67147 ADHESIVE VANCHEM HM50
MANF: R T VANDERBILT
....NO TEST DATA AVAILABLE....

20705 ADHESIVE VELODUR METAL/EPOXY GID: ABBGGI
MANF: AMERICAN VELODUR INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.080	0.003	00.00	00.00	NONE
B	1	025.9	014.3	0.080	0.003	00.02	09.30	SMALL
X	2	025.9	014.3	0.089	0.003		00.10	NONE
X	1	025.9	014.3	0.089	0.003	00.15	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.35	.36	.00	18H-46F-0psiaVACUUM

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00017.85	16H-70F-

05626 ADHESIVE VERSALON XR1200 POLYAMIDE GID: ABXXXX
MANF: GENERAL MILLS
....NO TEST DATA AVAILABLE....

66889 ADHESIVE VERSAMID 125
MANF: HENKEL
....NO TEST DATA AVAILABLE....

65191 ADHESIVE VERSAMID 140 GID: ABXXXX
MANF: HENKEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	030.0	010.0		0.003	00.90	07.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00023.30	

66967 ADHESIVE VERSILOK 101
MANF: LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.47	.63	.00	24H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

66956 ADHESIVE VERSILOK 201
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66957 ADHESIVE VERSILOK 202
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005387 7

66958 ADHESIVE VERSILOK 204
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66959 ADHESIVE VERSILOK 506
MANF: LORD CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	4.06	.10	.00	SEE TEST REPORT	No test data		

66960 ADHESIVE VERSILOK 510
MANF: LORD CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.23	.01	.00	SEE TEST REPORT	No test data		

66961 ADHESIVE VERSILOK 513
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66962 ADHESIVE VERSILOK 516
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66963 ADHESIVE VERSILOK 521
MANF: LORD CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.36	.00	.00	SEE TEST REPORT	No test data		

06553 ADHESIVE VERSILOK 528 ACRYLIC GID: ABAKXX
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66964 ADHESIVE VERSILOK 551
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66965 ADHESIVE VERSILOK 560
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

66966 ADHESIVE VERSILOK ACRYLIC
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

67107 ADHESIVE VITON PLV2002
MANF: PELMOR LABORATORIES
....NO TEST DATA AVAILABLE....

66415 ADHESIVE VOLAN 9720PP
MANF: DUPONT
....NO TEST DATA AVAILABLE....

67561 ADHESIVE WALLBOARD ADHESIVE #108
MANF: 3M CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005388 9

67564 ADHESIVE WEAR RESISTANT LIQUID #11220
MANF: 3M CO
....NO TEST DATA AVAILABLE....

67565 ADHESIVE WEAR RESISTANT PUTTY #11420
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83674 ADHESIVE WEATHERBAN 202
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83675 ADHESIVE WEATHERBAN 404
MANF: 3M CO
....NO TEST DATA AVAILABLE....

83676 ADHESIVE WEATHERBAN 606NF
MANF: 3M CO
....NO TEST DATA AVAILABLE....

65932 ADHESIVE WELDWOOD ACRYLIC LATEX CONTACT CEMENT
MANF: BEECHAM
....NO TEST DATA AVAILABLE....

65926 ADHESIVE WELDWOOD ALL WEATHER OUTDOOR CARPET
MANF: BEECHAM
....NO TEST DATA AVAILABLE....

65927 ADHESIVE WELDWOOD CARPET CEMENT
MANF: BEECHAM
....NO TEST DATA AVAILABLE....

65939 ADHESIVE WELDWOOD CONTACT CEMENT
MANF: BEECHAM
....NO TEST DATA AVAILABLE....

65944 ADHESIVE WELDWOOD HEAVY DUTY WALLCOVERING
MANF: BEECHAM
....NO TEST DATA AVAILABLE....

65928 ADHESIVE WELDWOOD MULTIPURPOSE FLOOR
MANF: BEECHAM
....NO TEST DATA AVAILABLE....

65933 ADHESIVE WELDWOOD ORIGINAL CONTACT CEMENT
MANF: BEECHAM
....NO TEST DATA AVAILABLE....

65940 ADHESIVE WELDWOOD RUBBER MENDER
MANF: BEECHAM
....NO TEST DATA AVAILABLE....

65929 ADHESIVE WELDWOOD WALLCOVERING
MANF: BEECHAM
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005389 0

Information Handling Services, 2000

65946 ADHESIVE WESTAC 718
MANF: BONDED PRODUCTS
....NO TEST DATA AVAILABLE....

66635 ADHESIVE WILLBOND 10
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66636 ADHESIVE WOODBOND 285
MANF: FRANKLIN INTERNATIONAL
....NO TEST DATA AVAILABLE....

66922 ADHESIVE X-PERT PANEL ADHESIVE
MANF: KELLER PRODUCTS CO
....NO TEST DATA AVAILABLE....

00755 ADHESIVE X1160 PS GID: AFXXXX
MANF: 3M CO

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.010	0.003		02.70	NONE	No test data	No test data						

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	3.5E-6	4.66	.19		48H-300F- 24H-150F-	No test data		

66363 ADHESIVE XEA9369
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

85391 ADHESIVE XEA9394 EPOXY GID: ABXXXX
MANF: HYSOL/DEXTER

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	20.9	14.7	0.022	0.003	00.09	12.00	T LARGE	No test data	No test data						

05967 ADHESIVE XFBC543 GID: ABXXXX
....NO TEST DATA AVAILABLE....

67015 ADHESIVE XL279
MANF: MERECO
....NO TEST DATA AVAILABLE....

65789 ADHESIVE XLC C860-1
MANF: AMICON
....NO TEST DATA AVAILABLE....

65791 ADHESIVE XLC C940-2
MANF: AMICON
....NO TEST DATA AVAILABLE....

65792 ADHESIVE XLC C940-4
MANF: AMICON

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.08	.00	.00	.17H-338F- .17H-518F-	No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005390 7

60690 ADHESIVE XR5038 EPOXY GID: ABBGXX
MANF: 3M CO
SPEC: MB0130-025

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.015		00.00	00.00	NONE
A	1	020.9	014.7	0.015			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.4E-6	4.50	.57		24H-280F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00018.40	SEE TVS CURE1

06411 ADHESIVE XR5135 EPOXY GID: ABBGXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

65793 ADHESIVE XT5235
MANF: AMICON
....NO TEST DATA AVAILABLE....

06183 ADHESIVE Z50 ACRYLIC GID: ABAKXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010	0.010	00.00	00.00	NONE
A	1	033.0	014.3	0.010	0.010		01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00022.24	

20779 ADHESIVE ZIPGRIP 10 GID: ABXXXX
MANF: DEVCON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	030.0	009.0	0.001	0.003		02.20	NONE
B	1	100.0	020.2	0.001	0.003		06.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.4E-6	11.00	.00	.48	24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00003.68	24H-70F-

66271 ADHESIVE ZIPGRIP 100
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66272 ADHESIVE ZIPGRIP 1500
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66273 ADHESIVE ZIPGRIP 5
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66274 ADHESIVE ZIPGRIP 50
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

66275 ADHESIVE ZIPGRIP SUPER GLUE
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005391 9

66416 ADHESIVE ZIRCORE FOUNDRY SAND
MANF: DUPONT
....NO TEST DATA AVAILABLE....

60404 AHH 847
....NO TEST DATA AVAILABLE....

05168 ALCOHOL CETYL ADOL 52NF GID: CZXXXX
MANF: ASHLAND CHEM

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data						A	A	00020.00	

20226 ALCOHOL RESIN POLYVINYL COMPAR
....NO TEST DATA AVAILABLE....

65288 ALCOHOL WIPES HRI8026-4204-0
MANF: PTIZER

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							X	00123.72	

64804 ALTITUDE OXYGEN HOSE GID: FEDPXX
MANF: SIERRA ENGINEERING

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.050			04.20	NONE	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	00228.73	

60378 AMCERMET 701-M65
MANF: ASTRO MET
....NO TEST DATA AVAILABLE....

65244 ANTENNA MATL KEV/KAP/EPOXY
MANF: CIBA-GEIGY
CONTRAVES

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
		020.9	014.7					NONE	No test data		No test data							

20758 ANTI-FOG SOLUTION P/N 350AF GID: DDXXXX
MANF: AMERICAN OPTICAL SPEC: ST64X366-01

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	4.2E-6	78.97	3.02	.	24H-70F-		V	00019.93	24H-70F-

60483 ANTI-PERSPIRANT DIAL UNSCENTED GID: DDXXXX
MANF: DIAL INDUSTRIES

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	00120.09	

60417 ARCOSET
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005392 0

62870 ARMALON
MANF: DUPONT
SPEC: TG-4060

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-220	0.006	1	60
B	MECH	600.0	72	-220	0.090	00	20

69813 ARMALON IMPREGNATED WITH KRYTOX 143 AZ
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	-297	0.050	00	20
B	MECH	1000	72	-297	0.090	00	20

05975 ARMALON TG 4102 GID: BFEFXX
MANF: DUPONT
....NO TEST DATA AVAILABLE....

60687 ARMALON TG 4140 GID: BFXXXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.014			01.10	SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00014.58	

02477 ARMALON XT 7XXXX GID: BFXXXX
MANF: DUPONT
....NO TEST DATA AVAILABLE....

61703 ATTENUATION PAD HRH-10 1/8-4.0 GID: FJBXBV
MANF: HEXCEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	4.000		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63192 B150L FIBERGLASS REINFORCED GID: DIGDXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.8	014.3	0.056			02.00	SMALL
A	1	030.0	009.0	0.056			02.70	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63456 BAG CAMERA GID: BFXXXX
MANF: ATAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.467		00.13	01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20274 BAG CONTINGENCY P/N 47A232804 GID: EXXXXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5			00.46	09.80	T SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00035.86	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005393 2

62728 BAG MINIGRIP POLYETHYLENE GID: DECCXX
MANF: MINIGRIP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.004		00.26	08.70	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00031.10	

62729 BAG NYLON MESH X-1591 GID: DEBSCQ
MANF: GRACE CHEMICAL
SPEC: MIL-D-3464T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.3	0.250		00.08	03.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63468 BAG NYLON/POLYETHYLENE/RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00710.10	

20412 BAG PLASTIC INTERLOCKING CLOSR GID: DKXXXX
MANF: GSA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.008		00.42	11.90	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.15	

63662 BAG POLYETHYLENE RCAS 1200 GID: DECCXX
MANF: DIXICO
SPEC: MIL-B-81705T11

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00104.30	

63880 BAG RECLOSABLE POLYURETHENE GID: DEXXXX
MANF: MINIGRIP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00034.90	

63858 BAG ZIP LOCK VINYL ACETATE GID: DEXXXX
MANF: EPD INDUSTRIES
GSA

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00044.70	

63990 BANDAGE ELASTIC ADHESIVE GID: DJXXXX
MANF: BEIERSDORF INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00022.01	

20848 BANDAGE MOLESKIN GID: BFXXXX
MANF: AMERICAN WHITE CROSS LABS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.050	0.003	03.01	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005394 4

20848 BANDAGE MOLESKIN (cont)

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.050	0.003	12.00	12.00	T NONE										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	A	00020.05	

20067 BARIUM FERRITE (INORGANIC) GID: DDXXXX

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.00	.00		

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
No test data			

63469 BARRIER FIBERTRAX HOTBOARD
MANF: CARBORUNDUM

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									S		No test data							

63457 BATTERY CELL ZN-AIR 630HP GID: EZXXXX
MANF: GOULD

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	A	00021.46	

65082 BATTERY CR2430 3V LITHIUM GID: XXXXXX
MANF: SANYO

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	V	00004.08	

20719 BATTERY DRY BA1568/U 14 VOLTS GID: EZXXXX
MANF: DURACELL U S A

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	K	00139.80	

20718 BATTERY DRY K308A P4-01-0008 GID: ESBYMQ
MANF: CHROMALLOY AMERICAN

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	K	00402.22	

63758 BATTERY DURACELL 9 VOLT MN1604
MANF: DURACELL U S A

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	K	00137.32	

20587 BATTERY DURACELL HG RM12R 1.35 GID: FCXXXX
SPEC: ST20M852-01
MANF: DURACELL U S A

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	A	00041.09	

20562 BATTERY DURACELL HG SIZE AA/ZM9 GID: EXXXXX
MANF: DURACELL U S A

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005395 6

20562 BATTERY DURACELL HG SIZE AA/ZM9 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00022.48	

80075 BATTERY DURACELL SIZE AA MN1500

MANF: DURACELL U S A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	83.086	

80086 BATTERY EVERREADY ENERGIZER E91 SIZE AA

MANF: UNION CARBIDE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	90.732	

65125 BATTERY LITHIUM LF 1/2W GID: EZGHXX

MANF: SANYO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00008.10	

61159 BATTERY MALLORY PX288 GID: EXXXXX

MANF: DURACELL U S A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00022.75	

65200 BATTERY NI/CD 5/600KZ 6V GID: FCXXXX

MANF: VARTA BATTERIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00138.17	

20585 BATTERY NI/CD CADNICA W10000M

....NO TEST DATA AVAILABLE....

20584 BATTERY NI/CD RECHARGE 7.0SC GID: FCXXXX

MANF: GOULD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	01263.00	

80078 BATTERY RAYOVAC ALKALINE SIZE AA

MANF: RAYOVAC CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	90.412	

80085 BATTERY SUPRALIFE GOLD TIPPED KAA4 SIZE AA

MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	96.392	

MSFC-HDBK-527 REV F 9999942 0005396 8

Information Handling Services, 2000

20612 BATTERY THIONYL CHLORIDE GID: EZXXXX
MANF: SEE TEST REPORT/HAZ TEST
TADIRAN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00018.10	

60431 BEADS GLASS SODALIME TY SILICA
MANF: POTTER CORP SPEC: MIL-G-9954
....NO TEST DATA AVAILABLE....

20281 BEARING BARDEN P/N 605172 GID: AHXXXX
MANF: BARDEN CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	30.88	1.08		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00000.82	

60140 BEESWAX CB191
....NO TEST DATA AVAILABLE....

63436 BELLOWS/TUBE FLEXAFIT SG2212 GID: FCXXXX
MANF: ESA/ERNO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.035			01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64294 BELT (TIMING) POLYURETHANE
MANF: MITSUBISHI

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.200		00.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00022.37	

62489 BELT POLYFLEX 8C84C077 COTTON/POLYESTER GID: CHCBFS
MANF: GATES MFG CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.139		00.20	09.30	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05351 BERYLLIA (BEO 99.5%) INORGANIC
MANF: SPEC: MIL-I-10A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025		00.00	00.00	NONE
A	1	023.8	014.7	0.025		00.00	00.00	NONE
A	1	024.5	014.7	0.025		00.00	00.00	NONE
A	1	025.9	014.7	0.025		00.00	00.00	NONE
A	1	030.0	014.7	0.025		00.00	00.00	NONE
A	1	100.0	014.7	0.025		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X		

60446 BLADDER BUTYL RUBBER GID: DOCZXX
MANF: AGC INC SPEC: ASTM 2AA508A13

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005397 T

60444 BLADDER BUTYL RUBBER (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.040		00.02	12.00	T MOD
X	1	025.9	014.3	0.040		00.71	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.0E-7	1.38	.53		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.39	

20874 BLADDER NEOPRENE 3N868 NO4/6 GID: DOGGXX

MANF: GENERAL LATEX SPEC: SVHS 9444

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	020.2	0.036		00.45	12.00	T MOD
X	1	100.0	020.2	0.036		01.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.11	.05	.39	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.28	

61154 BLADDER URETHANE GID: DVCQXX

MANF: ILC DOVER SPEC: ST43P138-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.041		00.24	12.30	T MOD
X	1	025.9	014.3	0.041			07.60	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	20	72	120	0.038	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	1.62	.03		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00010.02	

20669 BLADE RAZOR DOUBLE EDGED PLATE

MANF: GILLETTE

....NO TEST DATA AVAILABLE....

61043 BLADES RAZOR SCHICK SUPER II GID: FCXXXX

MANF: WARNER LAMBERT CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00016.59	

20521 BLANKET SURVIVAL SPACE BRAND GID: CMFJXX

MANF: KING SEELEY THERMOS SPEC: ST11B823

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00052.23	

60702 BLOWER BRAILSFORD MODEL TB1-1 GID: FCXXXX

MANF: BRAILSFORD & CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00193.47	

06025 BOARD DRAWING 4-PLY

....NO TEST DATA AVAILABLE....

61238 BOOT 05078 LEATHER/NYLON GID: FGFPBS

MANF: DEHNER CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	01039.96	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005398 1

60076 BORON 2A
....NO TEST DATA AVAILABLE....

60077 BORON GRANDULES
....NO TEST DATA AVAILABLE....

05776 BORON NITRIDE (INORG)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.93	.04	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

63459 BOTTLE VACUUM #SL-4VBA
MANF: L & M ELECTRONICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00030.40	

63458 BOTTLE VACUUM SERIES #2
MANF: L & M ELECTRONICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	00030.26	

63470 BOX APEX TAPE GID: EXXXXX
MANF: APEX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	10722.00	

62730 BRAID ELASTIC NYLON/RUBBER GID: BHBSXX
MANF: DRITZ

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.032		00.11	07.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61371 BRAID ELASTIC POLYESTER GID: BHCBXX
MANF: DRITZ
SCOVILL
SPEC: ST13E813-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.035		00.96	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.10	.49		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00008.89	

20408 BRAID ELASTIC POLYESTER/RUBBER GID: BHXXXX
MANF: SCOVILL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.037		00.93	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	6.0E-6	2.27	.54		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00020.12	

20630 BRAID NOMEX COVER/HARNESS GID: FFXXXX
MANF: ATLAS CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005399 3

63797 BRAID NYLON ELASTIC GID: BHBSXX
MANF: DRITZ

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00005.70	

TOXICITY

05965 BRAKE MATERIAL 4813
....NO TEST DATA AVAILABLE....

20097 BRAKE MATERIAL F328 CORK COMP GID: AHFRXX
MANF: DODGE CORK CO INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.130			01.50	NONE
X	1	023.8	014.5	0.130		00.15	11.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.3E-6	10.43	.69		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61610 BRAKE MATERIAL M4952 GID: BBXXXX
MANF: RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.118		00.00	00.00	NONE
A	1	033.0	014.3	0.118			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.4E-6	.99	.05		

ODOR

RT	RT WEIGHT	CURE
A	00019.82	

TOXICITY

05165 BRAKE MATERIAL R3672-7
....NO TEST DATA AVAILABLE....

00633 BRAKE MATERIAL R740 BTG GID: CPFLXX
MANF: RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.058			00.20	NONE
A	1	023.8	014.5	0.058			03.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00020.18	

TOXICITY

06397 BRAKE MATERIAL S1698-5 GID: AHXXXX
MANF: RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.122		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.3E-6	.52	.00	.33	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20448 BRAKE MATERIAL S451 GID: DTFLXX
MANF: RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.250		00.00	00.00	NONE
A	1	033.0	014.3	0.250			00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0005400 6

Information Handling Services, 2000

20448 BRAKE MATERIAL S451 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.67	.00		60H-70F-

ODOR

RT	RT	WEIGHT	CURE
	A	00020.22	

TOXICITY

05324 BRAKE MATERIAL SD1240B GID: AHXXXX

....NO TEST DATA AVAILABLE....

64028 BRUSH AL/WOOD/CAMEL HAIR

MANF: CRUMBACHER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00001.26	

TOXICITY

20689 BRUSH STYLING ALUMINUM JATCO

....NO TEST DATA AVAILABLE....

20715 BUTTON IRIDES WHT PE 21/4 HOLE

....NO TEST DATA AVAILABLE....

80102 CABLE 77 OHM TWINAX

MANF: THERMAX WIRE CORP

SPEC: MIL-C-17/176B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.128			00.80	SMALL

FSC

RT	FLUID NAME
No test data	

MIL-C-175

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	10.420	

TOXICITY

61825 CABLE ASSEMBLY NYLON/GLASS GID: EMBSIA

MANF: SPECTRA-STRIP CORP

SPEC: SV755622-4

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	4	023.8	014.5	0.500			00.00	NONE
X	1	023.8	014.5	0.500			02.60	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	023.8	014.5	0.500	02.60	00.00

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.7E-7	1.58	.02		

ODOR

RT	RT	WEIGHT	CURE
	A	00019.53	

TOXICITY

61477 CABLE CLAMP NE 127-0071 GID: BDDPFK

MANF: J & M PRODUCTS
ROCKWELL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.813	0.032		00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.74	.29	.03	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

63906 CABLE COAX

....NO TEST DATA AVAILABLE....

63296 CABLE COAX CU/AU 250-3866-0000 GID: EOHNJE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.01	.00	.00	

ODOR

RT	RT	WEIGHT	CURE
	K	00033.50	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005401 8

62461 CABLE COAX RG142 PTFE CORE FEP JACKET SILVER COATED COPPER GID: EOXXXX

MANF: DEARCOM WIRE & CABLE SPEC: MIL-C-17E12814

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0				00.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	A	00021.71	

69963 CABLE COAX RG179 PTFE CORE FEP JACKET SILVER COATED COPPER

MANF: W L GORE SPEC: MIL-C-17

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.010			01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
A	K	22.40	

65462 CABLE COAX RG188 GID: EOXXXX

MANF: BELDEN
DEARCOM WIRE & CABLE
TIMES WIRE & CABLE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.100			01.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	164.7	72	70	0.106	00	20
B	MECH	164.7	72	-250	0.106	00	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.01	.00	.00	

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	K	00020.99	

69968 CABLE COAX RG6178 PTFE CORE FEP JACKET SILVER COATED COPPER

MANF: W L GORE SPEC: MIL-C-17

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.010			01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
A	K	10.307	

69942 CABLE COAX SILVER PLATED COPPER WITH PTFE KAPTON

MANF: ABLESTIK
FILISTER

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	020.9	014.7		01.30	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST.
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.0E-6	.12	.00	.09	

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
No test data			

62584 CABLE COAXIAL 26 AWG GID: EOXXXX

MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	4	020.9	014.7	0.001			00.00	NONE
A	1	020.9	014.7	0.001			02.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	020.9	014.7	0.001	02.90	00.00

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005402 T

62584 CABLE COAXIAL 26 AWG (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.00	.00	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

80112 CABLE COAXIAL RG-58C/U

MANF: MONTROSE PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	4	025.4	014.3				00.00	NONE
A	1	025.9	014.3				00.60	NONE
A	1	030.0	009.0				00.75	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	51.5	

05417 CABLE COAXIAL TFE/FEP GID: EOXXXX

MANF: TENSOLITE
UNIFORM TUBES

SPEC: MB0150-053
MB0150-057
MB0150-056
RG 3161U

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	4	100.0	044.0				12.00	T NONE
I	1	100.0	044.0	0.110		00.92	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.107	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00082.75	

80240 CABLE COAXIAL THERMAX RGU142 OVERLAID WITH EXPANDO NR HALAR SLEEVING GID: EOXXXX

MANF: BENTLEY HARRIS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0				00.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06420 CABLE CRES LUBRICATED GID: EMMDXX

MANF: ROCKWELL

SPEC: MIL-W-83420

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	.74	.33	.01	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00009.02	

62303 CABLE EIM GID: EFXXXX

MANF: NASA/JSC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	00182.41	

62016 CABLE ELEC CAMERA/PVC INSULATION GID: EMAEXX

MANF: NIKON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	4	025.9	014.3	0.161			00.00	NONE
X	1	025.9	014.3	0.161		00.32	13.20	T MOD
X	1	025.9	014.3	0.200		00.16	13.20	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	025.9	014.3	0.161	13.20	00.00

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	00029.41	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005403 1

63961 CABLE ELEC COONER AS155-28-2SJ GID: EMXXXX

MANF: COONER WIRE CO

ELECTRICAL WIRE & ACCESSORIES						FSC	OXYGEN COMP				
RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	025.9	014.3	0.108	12.00		No test data	No test data				
X	030.0	010.0	0.108	12.00	00.00						

65023 CABLE ELEC EF-2PWMS HIFLON GID: EXXXXX

MANF: NISSEI ELECTRIC CO

ELECTRICAL WIRE & ACCESSORIES						FSC	OXYGEN COMP				
RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	024.5	014.5	0.170	12.00	00.30	No test data	No test data				

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	00021.53	

63413 CABLE ELEC WILCO/TFE/NYLON/NOMEX/AL

MANF: NASA/MSFC

ELECTRICAL WIRE & ACCESSORIES						FSC	OXYGEN COMP				
RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
B	020.9	014.7		01.00	01.00	No test data	No test data				

63418 CABLE ELEC PTFE WITH SHEATH TAPE GID: EPCOXX

MANF: QUIRK WIRE CO SPEC: STM-E-300-1

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
C	1	100.0	014.3			00.16	12.00	T SMALL	No test data	No test data				

62857 CABLE ELEC RTM437 CU IMBEDDED IN FEP WITH TEFLON OVERWRAP GID: CKBOXX

MANF: HAVEG SPEC: MMS-E-658 1010 RTM 437 E 658

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
I	1	100.0	044.0			00.75	12.00	T SMALL	No test data	No test data				
X	4	100.0	044.0	0.133			12.00	T NONE						

63411 CABLE ELEC TFE/BEN-HAR GLUE GID: EPCNXX

MANF: BENTLEY HARRIS SPEC: MMS-E-300 MMS-E-3002002
IMPERIAL WIRE & CABLE STM-E-300

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	4	100.0	042.0	0.032			00.00	NONE	No test data	No test data				
A	1	100.0	042.0	0.032			00.50	NONE						

ELECTRICAL WIRE & ACCESSORIES					
RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	100.0	042.0	0.032	00.50	00.00

63410 CABLE ELEC TFE/BEN-HAR SLEEVE GID: EPCNXX

MANF: QUIRK WIRE CO SPEC: MMS-E-300 STM-E-300

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
C	4	100.0	042.0	0.032			07.75	NONE	No test data	No test data				
C	1	100.0	042.0	0.032			00.50	NONE						

63409 CABLE ELEC TFE/VARGLAS SLEEVE GID: EPCNX

MANF: QUIRK WIRE CO SPEC: MMS-E-300 STM-E-300
STM-E-300-1

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
C	4	100.0	042.0				12.00	T NONE	No test data	No test data				

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005404 3

63409 CABLE ELEC TFE/VARGLAS SLEEVE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	100.0	042.0			00.03	18.00	T NONE

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
C	100.0	042.0		18.00	12.00

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS.	IMPACT	TEMP	THICK	#REACT	#TEST

63417 CABLE ELEC TFE/VARGLAS SLEEVE GID: EPCNXX

MANF: CARLISLE CORP SPEC: MMS-E-300 STM-E-300

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	100.0	042.0			00.120	06.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64207 CABLE ELEC URETHANE J210/BLK GID: EMDUXX

MANF: W L GORE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.148		00.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80275 CABLE ELECTRICAL 07145 AG COATED CU WITH TEFLON AND ALUMINIZED MYLAR GID: EMXXXX

MANF: TIMES FIBER SPEC: MIL-C-17/60 SF-142B

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	025.9	014.3	0.200	00.25	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.0E-6	.49	.12	.03	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

80274 CABLE ELECTRICAL SEA BL125 GID: EMXXXX

MANF: SEA WIRE AND CABLE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.03	.01	.00	

ODOR

RT	RT WEIGHT	CURE
	X	

TOXICITY

80191 CABLE F-12PWMS HIFLON GID: EMXXXX

MANF: NISSEI ELECTRIC CO

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	024.5	014.5		12.00	04.30

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	K 22.055	

TOXICITY

80279 CABLE FIBER OPTIC OC-1050 GID: EMXXXX

MANF: BRAND REX CORP

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	030.0	009.0	0.082	01.00	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	K 06.00	

TOXICITY

80277 CABLE FIBER OPTIC VSC-A1-10-17 GID: EMXXXX

MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.057		0.10	06.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005405 5

80277 CABLE FIBER OPTIC VSC-A1-10-17 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	02.00	

63760 CABLE HARNESS 3AFT 23-15

MANF: L & M ELECTRONICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00163.28	

63422 CABLE HARNESS ASSEMBLY QUIRK 22AWG GID: EZFVCN

MANF: MMC-MAF

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	4	100.0	042.0				12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	100.0	042.0			12.00

63434 CABLE HARNESS ASSEMBLY/TFE/BEN-HAR GID: FFXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	4	100.0	042.0	0.032			00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	100.0	042.0	0.032		00.00

85433 CABLE HIGH VOLTAGE RUBBER SILICONE INSULATED WITH VITON SLEEVING GID: EMXXXX

MANF: GTE SPEC: P/N 2032

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.500		00.02	00.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65139 CABLE IEEE 488 GID: ENXXXX

MANF: GRID COMPUTER CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00366.34	

62259 CABLE INSULD/FES 51 REFL TAPE GID: EPXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	014.7	1.250			01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62260 CABLE INSULD/ST8000X/FES 51 GID: EPXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	014.7	2.140			01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62258 CABLE INSULD/TEFLON 5481 TAPE GID: EPCOXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	014.7	1.087			00.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61380 CABLE MICROPHONE GID: EXXXXX

MANF: ASTROCOM

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005406 7

61380 CABLE MICROPHONE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.400		00.17	07.10	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00011.95	

80196 CABLE MULTI JUNFLON 854-048A PTFE GID: EMXXXX

MANF: JUNKOSHA CO LTD

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	024.5	014.5	0.029	00.00	00.10

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	22.129	

62302 CABLE OSCILLOSCOPE GID: EFXXXX

MANF: NASA/JSC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00034.89	

85392 CABLE SPLICE NAS1744

MANF: AQM

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	025.9	014.3	0.180	00.50	12.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61970 CABLE TIES MOUNT TC103 NYLON GID: DKBSXX

MANF: THOMAS & BETTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	2.43	.02		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

64220 CABLE TIES NOMEX/POLYETHYLENE FC4101 GID: BMBVXX

MANF: 3M CO/ROCKWELL
BALLY RIBBON MILLS
MIDDLETOWN

SPEC: MAO105-330
MIL-T-5038
MIL-T-43636

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.060			03.40	SMALL
A	1	030.0	010.0	0.060			03.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	025.9	014.3	0.060	03.40	
I	030.0	010.0	0.060	03.60	

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	K 00022.89	

62741 CABLE TIES PAN-TY HALAR GID: ECJLXX

MANF: PANDUIT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.044			02.00	NONE
A	1	030.0	010.0	0.800			01.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005407 9

62741 CABLE TIES PAN-TY HALAR (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.4E-6	.17	.00	.02	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	A	00020.00	

62742 CABLE TIES PAN-TY TEFZEL GID: ECJKXX

MANF: PANDUIT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.044			02.00	MOD
X	1	030.0	010.0	0.044			02.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.4E-6	.10	.00	.00	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	V	00019.50	

05205 CABLE TIES TEFZEL TY-RAP TYZ GID: ENDFXX

MANF: THOMAS & BETTS

SPEC: MIL-W-22759
STSV 438

P/N TYZ527M

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.046			00.10	NONE
X	1	025.9	014.3	0.060		00.06	07.30	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	020.9	014.7		02.50	
I	023.8	014.5	0.012		00.50
X	024.5	014.5	0.073		03.25
X	025.9	014.3	0.046	07.30	00.10
B	030.0	009.0	0.046	01.60	00.01
X	100.0	019.0			12.00

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.98	.01	.00	24H-257F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	A	00020.07	

62739 CABLE TIES TY-27M NYLON GID: ECBSXX

MANF: THOMAS & BETTS

SPEC: MIL-S-23190D

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.062		00.06	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.45	.01	.00	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	K	00025.30	

62740 CABLE TIES TY-28M NYLON GID: ECBSXX

MANF: THOMAS & BETTS

SPEC: MIL-S-23190D

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5				01.50	MOD
X	1	024.5	014.5	0.031		00.11	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63505 CALSPAN SEAL SETS 67/151007 GID: CHXXXX

MANF: CALSPAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	3000	72	72	0.040	0	40

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005408 0

60748 CAN RODENT GID: FCXXXX
MANF: AMES METAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00166.92	

TOXICITY

63714 CAP DISPENSER TOOTHPASTE GID: EXXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00003.21	

TOXICITY

61355 CAPACITOR EMI TVA1966 GID: FCXXXX
MANF: SPRAGUE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00053.17	

TOXICITY

62550 CAPLUGS PVC EC22 CANNON 500 GID: DKAEXX
MANF: ITT CANNON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.032		00.38	01.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60291 CARBON BLACK
MANF: AQM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.77	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61642 CARBON FIBER TOW AS4W
MANF: HERCULES
....NO TEST DATA AVAILABLE....

60107 CARBON GRAPHITE BRUSH MATERIAL
....NO TEST DATA AVAILABLE....

05488 CARBON GRAPHITE MOLD MECH GID: AHGFXX
MANF: UNION CARBIDE SPEC: MB0115-018

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-7	.06	.01		

ODOR

RT	RT WEIGHT	CURE
A	K 00020.45	

TOXICITY

06641 CARBON GRAPHITE PUREBOND P9193 GID: BBMJGF
MANF: UNION CARBIDE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00022.34	

TOXICITY

62895 CARBON P9

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	72	-297	0.050	0	20

05112 CARBON/GRAPHITE BONDED
MANF: LTV AEROSPACE CORP
SUPER-TEMP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.6E-6	.04	.01		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005409 2

61042 CARDS CUE PAPER GID: DICCXX
MANF: INTERNATIONAL PAPER
SCOTT PAPER CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	X	00020.10	

TOXICITY

64090 CARTRIDGE DATA DC 300A GID: FCXXXX
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00298.12	

TOXICITY

69895 CAST CAROPLASTIC PROPOSED FOR PPE
MANF: UAH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	X	504.4	

TOXICITY

61799 CELCON G-C25 ACETAL/25% GLASS GID: DKAJXX
MANF: CELANESE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.4E-7	.34	.02		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60786 CELCON M-90-24 ACETAL POLYMER GID: BNAJXX
MANF: CELANESE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.64	.04	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05432 CELCON WHITE GID: BNAJXX
MANF: CELANESE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	015.0	014.3	0.056		00.06	12.00	T MOD
X	1	017.0	014.3	0.057		00.07	12.00	T MOD
I	1	019.0	014.3	0.058		00.16	12.00	T NONE
X	1	023.8	014.5	0.060		00.11	12.00	T MOD
X	1	030.0	008.0	0.055		00.11	12.00	T MOD
X	1	040.0	008.0	0.055		00.11	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.7E-6	.36	.01		

ODOR

RT	RT	WEIGHT	CURE
A	V	00122.60	

TOXICITY

20123 CELLULOSE ACETATE
MANF: ARTUS CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	10.70	1.19	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05666 CEMENT #78 (INORG) GID: ABHOXV
MANF: SAUEREISEN CEMENT CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	MECH	100	72	500	0.055	0	20
A	MECH	14.7	72	-297	0.011	0	40

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005410 9

05666 CEMENT #78 (INORG) (cont)

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
											A	MECH	260	72	70	0.018	0	20
											B	PNEU	260		70	0.018	0	20
											A	MECH	285	72	200	0.018	0	20
											B	PNEU	285		200	0.032	0	20
											B	PNEU	50		500	0.018	0	20

05550 CEMENT FUSED SILICA INORGANIC
MANF: SPEC: MB0120-085
....NO TEST DATA AVAILABLE....

06203 CERAMIC 5656 (INORG) GID: DOHOHO
MANF: 3M CO

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.025		00.00	00.00	NONE	No test data		No test data							
A	1	023.8	014.7	0.025		00.00	00.00	NONE										
A	1	024.5	014.7	0.025		00.00	00.00	NONE										
A	1	025.9	014.7	0.025		00.00	00.00	NONE										
A	1	030.0	014.7	0.025		00.00	00.00	NONE										
A	1	100.0	014.7	0.025		00.00	00.00	NONE										

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	1.0E-6	.16	.06	.05			A	00043.37	

06578 CERAMIC AB312 FABRIC/ACRYLIC/FC723 GID: DOHOHO
MANF: 3M CO SPEC: MB0135-066/CTD
ROCKWELL

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.037			04.60	NONE	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	1.0E-6	.16	.06	.05		No test data			

05998 CERAMIC AB312 FABRIC/POLYETHYLENE GID: DOHOHO
MANF: N L INDUSTRIES SPEC: MA0609-308T1 MB0135-065

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.045		00.00	00.00	NONE	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	2.0E-6	.43	.07	.01		No test data			

06577 CERAMIC AB312 FABRIC/POLYSULFONE/FC723 GID: DOHOHO
MANF: 3M CO SPEC: MB0135-066/CTD
ROCKWELL

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.038			01.90	NONE	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	2.2E-6	.96	.02	.05		No test data			

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005411 0

06071 CERAMIC AD995 ALUMINA (INORG) GID: DOHOHO

MANF: COORS PORCELAIN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	MECH	14.7	72	70	0.097	0	20
A	MECH	275	72	200	0.125	0	20
B	PNEU	275		70	0.025	0	20
A	MECH	275	72	70	0.125	0	20
B	PNEU	500		200	0.062	0	20

05534 CERAMIC ALSIMAG 35 (INORGANIC) GID: DOHOHO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025		00.00	00.00	NONE
A	1	023.8	014.7	0.025		00.00	00.00	NONE
A	1	024.5	014.7	0.025		00.00	00.00	NONE
A	1	025.9	014.7	0.025		00.00	00.00	NONE
A	1	030.0	014.7	0.025		00.00	00.00	NONE
A	1	100.0	014.7	0.025		00.00	00.00	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.16	.06	.05	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00043.37	

05663 CERAMIC ALSIMAG 771 (INORG) GID: DOHOHO

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	14.7	72	-297	0.020	0	12
A	MECH	260	72	500	0.059	0	20
B	PNEU	260		70	0.055	0	20
B	PNEU	285		200	0.055	0	20
A	MECH	285	72	200	0.060	0	20
B	PNEU	50		500	0.055	0	20
A	MECH	50	72	500	0.059	0	20

05352 CERAMIC ALUMINA AD-96 GID: DOHOHO

MANF: COORS PORCELAIN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.002			04.30	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.43	.07	.01	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00022.55	

20055 CERAMIC ALUMINO-SILICAT P1/2BC GID: DOHOHO

MANF: COORS PORCELAIN

....NO TEST DATA AVAILABLE....

06541 CERAMIC BERYLLIUM OXIDE (INOR) GID: DOHOHO

....NO TEST DATA AVAILABLE....

06212 CERAMIC BRAID SLEEVING SF2600 GID: BMHOHO

MANF: SANTA FE TEXTILES

SPEC: MB0135-066

....NO TEST DATA AVAILABLE....

20280 CERAMIC CAPACITOR P/N AOL0044 GID: DOHOHO

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005412 2

05696 CERAMIC CEMENT PBX GID: DOHDHO

....NO TEST DATA AVAILABLE....

60321 CERAMIC CEMENT PS-1027 GID: DOHOHO

MANF: HY-CAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025		00.00	00.00	NONE
A	1	023.8	014.7	0.025		00.00	00.00	NONE
A	1	024.5	014.7	0.025		00.00	00.00	NONE
A	1	025.9	014.7	0.025		00.00	00.00	NONE
A	1	030.0	014.7	0.025		00.00	00.00	NONE
A	1	100.0	014.7	0.025		00.00	00.00	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.16	.06	.05	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00043.37	

60320 CERAMIC CEMENT PS-1032 GID: DOHOHO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025		00.00	00.00	NONE
A	1	023.8	014.7	0.025		00.00	00.00	NONE
A	1	024.5	014.7	0.025		00.00	00.00	NONE
A	1	025.9	014.7	0.025		00.00	00.00	NONE
A	1	030.0	014.7	0.025		00.00	00.00	NONE
A	1	100.0	014.7	0.025		00.00	00.00	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.16	.06	.05	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00043.37	

20482 CERAMIC DUROCK 101 GID: FJHOXX

MANF: GULTON INDUSTRIES

....NO TEST DATA AVAILABLE....

05459 CERAMIC DUROCK 117 GID: FJIAXX

MANF: GULTON INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	MECH	1000	72	70		0	20
B	PNEU	1000		70		0	20

06202 CERAMIC DUROCK 17 OR 33 GID: DOHOHO

MANF: GULTON INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025		00.00	00.00	NONE
A	1	023.8	014.7	0.025		00.00	00.00	NONE
A	1	024.5	014.7	0.025		00.00	00.00	NONE
A	1	025.9	014.7	0.025		00.00	00.00	NONE
A	1	030.0	014.7	0.025		00.00	00.00	NONE
A	1	100.0	014.7	0.025		00.00	00.00	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.16	.06	.05	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00043.37	

62215 CERAMIC DUROCK 204 GID: FJHOXX

MANF: GULTON INDUSTRIES

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005413 4

62215 CERAMIC DUROCK 204 (cont)

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		A	MECH	1000	72	-297	0.136	0	20
											A	MECH	1050	72	200	0.136	0	20

20086 CERAMIC INSULATOR MATERIAL GID: DOHOHO
MANF: 3M CO
....NO TEST DATA AVAILABLE....

06142 CERAMIC LITHAFRAX (INORGANIC) GID: DOHOHO
....NO TEST DATA AVAILABLE....

06055 CERAMIC MACOR (INORGANIC) GID: DOHOHO
MANF: DURAMIC PRODUCTS SPEC: MB0115-024

THERMAL VACUUM STABILITY						ODOR			TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	1.0E-6	.01	.00	.00		No test data			

05252 CERAMIC MICROCIRCUIT/INORGANIC GID: DOHOHO
MANF: SPEC: MIL-M-38510
....NO TEST DATA AVAILABLE....

06466 CERAMIC NEXTEL XC-568 F12 INOR GID: DOHOHO
MANF: 3M CO
....NO TEST DATA AVAILABLE....

60059 CETYL ALCOHOL-FASTENR LUB ONLY
MANF: AQM

THERMAL VACUUM STABILITY						ODOR			TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.0E-6	99.45	68.35			No test data			

63717 CHAMBER MODULE CROSS SECTION GID: EXXXXX

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
S		20.9	14.7					NONE	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR			TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
S	5.0E-5					No test data			

20181 CHARCOAL (INORGANIC)
....NO TEST DATA AVAILABLE....

05408 CHARCOAL ACTIVATED NUCHAR 503
....NO TEST DATA AVAILABLE....

65039 CHEMFABRICS 1
MANF: CHEMICAL FABRICS

THERMAL VACUUM STABILITY						ODOR			TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	6.0E-6	.02	.03	.01		No test data			

65040 CHEMFABRICS 2
MANF: CHEMICAL FABRICS

THERMAL VACUUM STABILITY						ODOR			TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	6.0E-6	.05	.01	.01		No test data			

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005414 6

65041 CHEMFABRICS 3
MANF: CHEMICAL FABRICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.03	.01	.01	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

63438 CHEMPOL/BETA CLOTH/113-300
MANF: MARTIN MARIETTA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	3.000		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62743 CIRCUIT BREAKER HEINEMAN GID: FCXXXX
MANF: HEINEMAN ELECTRIC CO SPEC: AMI-B3-A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.3	0.625		00.01	01.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	00058.44	

85420 CLAMP 45L83 LOOP WITH SILICONE CUSHION GID: BDXXXX
MANF: AQM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.250			00.25	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63767 CLAMP CABLE ADEL 1408 GID: BDXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	03718.20	

64880 CLAMP CABLE P/N 10020-24 GID: BDXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00682.30	

65340 CLAMP CUSHION FLOUROSILICONE GID: DOEGXX
MANF: UMPCO SPEC: MS21919WCJ7

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.6E-6	.22	.00	.05	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

61870 CLAMP CUSHION SILICONE/FIBERGLASS CL 3B GR 60 GID: BDCKFV
MANF: UMPCO SPEC: ME127-0071-3016 ZZ-R-765 CL 3B GR 60

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.056			07.70	SMALL
A	1	030.0	009.0	0.163			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	01.21	00.27		24H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00020.68	

65490 CLAMP CUSHION TA101 GID: AZXXXX
MANF: T A MFG CORP SPEC: C-85052

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.12	.01	.07	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005415 8

65169 CLAMP CUSHION TEFLON (13K) GID: BDCNXX
MANF: AQM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00142.50	

TOXICITY

61974 CLAMP ELECT NYLON/GLASS FILLED GID: BDBSIA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.224		00.02	01.10	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00007.47	

TOXICITY

63787 CLAMP FOR LEAD PLATES GID: BDXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00081.70	

TOXICITY

05309 CLAMP GE2449/13407-JM-RP GID: BDXXXX
....NO TEST DATA AVAILABLE....

80183 CLAMP HIGH THERMAL KCA-44 GID: BDXXXX
MANF: ASAHI GLASS CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.060			01.10	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	22.174	

TOXICITY

05336 CLAMP MS21919 WDG NEOPRENE GID: BNDBXX
MANF: SPEC: AMS 3209
....NO TEST DATA AVAILABLE....

61218 CLAMP NEOPRENE/AL MS21919DG GID: BDDBXX
MANF: QPL SPEC: MIL-C-8603

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.062			01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	X	00016.97	

TOXICITY

62746 CLAMP NYLON GID: BDBSXX
MANF: TRW

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.3	0.062		00.01	03.00	T MOD
X	1	030.0	010.0	0.062		00.02	03.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65393 CLAMP P/N TAS70T08X;4X;6X GID: BDXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00081.70	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005416 T

62744 CLAMP BL5033/CUSHION L32171 GID: BDXXXX
MANF: J & M PRODUCTS
RAYBESTOS-MANHATTAN
SPEC: STM-0564-020302

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.125		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05098 CLAMP SILICON/GLASS VB GID: BDCKIA

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.47	.00	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

61476 CLAMP SILICONE/CRES JM44 GID: BDDPMD
MANF: J & M PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.124		00.04	03.90	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.1E-6	.14	.00		

ODOR

RT	RT	WEIGHT	CURE
A	K	00015.86	

TOXICITY

63650 GLAMP SILICONE/FABRIC TA 321 GID: EXXXXX
MANF: T A MFG CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.41	.12		

ODOR

RT	RT	WEIGHT	CURE
	K	00035.60	

TOXICITY

02997 CLAMP SILICONE/GLASS GID: BDCKIA
MANF: CRITON CORP
T A MFG CORP
SPEC: ME127-0012-0016
MIL-R-3065
ME127-0028-7XXX
MIL-R-3065TA612

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.060		00.01	00.10	NONE
X	1	025.9	014.3	0.060		00.01	12.00	T MOD
A	1	030.0	009.0	0.192	0.032		00.20	NONE
X	1	030.0	010.0	0.060		00.06	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.85	.51	.00	

ODOR

RT	RT	WEIGHT	CURE
A	A	00010.06	

TOXICITY

62823 CLAMP SLEEVE TEFLON TFE GID: BNCOXX
MANF: T A MFG CORP
SPEC: MIL-P-22241

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.031	0	20
B	MECH	14.7	72	-297	0.046	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.01	.00	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

62745 CLAMP ST253/CUSH MOSITES 1059 GID: BNXXXX
MANF: INGLA RUBBER PRODUCTS
T A MFG CORP
SPEC: STM-0564-020302

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.125		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR

RT	RT	WEIGHT	CURE
	B	00064.30	72H-70F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005417 1

62747 CLAMP TA02112 WITH INSUL GID: BDXXXX
MANF: T A MFG CORP

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	024.5	014.3	0.050		00.03	00.70	NONE	No test data		No test data							

61631 CLAMP TEFLON PTFE GID: BDXXXX
....NO TEST DATA AVAILABLE....

61416 CLAMP WITH SILICONE INSERT GID: BDCKXX
MANF: ADEL

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5				00.10	NONE	No test data		No test data							

63489 CLEANER BRAYCOTE 137 GID: AKXXXX
MANF: BRAY OIL CO SPEC: MIL-C-16173G23

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	030.0	010.0		0.003		00.00	NONE	No test data		No test data							
C	1	030.0	010.0		0.003	01.50	12.00	T NONE										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	61.00	11.12	.03	24H-70F-

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
	X 00014.55	

62818 CLEANER FORMULA APC
MANF: MARKING METHODS

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	500	72	-297		0	20

62027 CLIPS CORD B2 GID: BNXXXX
MANF: WESTERN ELECTRIC SPEC: AT8598

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.107			02.40	NONE	No test data		No test data							

05198 COATING 02-GY-3 EPOXY GID: AKBGXX
MANF: DEFT SPEC: MB0125-070

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	2	023.8	014.5	0.005		00.00	00.00	NONE	No test data		No test data							
A	1	023.8	014.5	0.005			02.60	NONE										
A	1	030.0	009.0	0.004			02.00	NONE										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.61	.11	.00	1H-302F-
					2H-302F-

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
	X 00005.26	72H-70F-

64887 COATING 02-GY-3 WITH ARAMID LAMIN GID: AKBGXX
MANF: DEFT SPEC: MB0125-070 MB0130-127T3
HEXCEL

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	030.0	009.0	0.014		00.56	12.10	T SMALL	No test data		No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005418 3

64886 COATING 02-GY-3 WITH KEVLAR LAMIN GID: AKBGXX

MANF: DUPONT
HEXCEL

SPEC: MB0125-070 MB0130-127T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.014			01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62766 COATING 023-GW-3/CHEMGLAZE A276 P GID: RATXXX

MANF: DEFT
LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.004			00.10	NONE
A	1	030.0	010.2	0.004			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.97	.02	.00	24H-70F- 4H-150F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00028.10	1080H-70F-

61778 COATING 03-BK-28 WITH CATALYST GID: AKXXXX

MANF: DEFT

SPEC: MIL-C-83286B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.006		00.00	00.00	NONE
C	1	023.8	014.5	0.006		00.60	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.2E-6	7.39	.04	.55	24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.40	168H-70F- 24H-150F-

62060 COATING 03-BK-29 POLYURETHANE FLAT BLACK GID: AKCQBG

MANF: DEFT
DESOTO

SPEC: MIL-C-83286

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.020	00.00	00.00	NONE
A	1	023.8	014.5	0.009	0.030	00.00	00.00	NONE
A	1	023.8	014.5	0.003	0.040	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.4E-6	1.99	.05		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

61877 COATING 03-BK-29 PRIMER GID: ATBGCQ

MANF: DEFT
PRIMER/DESOTO

SPEC: MB0125-055

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	B 00009.00	SEE TEST REPORT

06586 COATING 03-BL-51 POLYURETHANE FLAT BLUE GID: ATCQXX

MANF: DEFT

SPEC: FED STD 595 MIL-C-83286

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		05.70	SMALL
I	1	025.9	014.3	0.002		00.60	12.00 T	NONE
A	1	030.0	010.4	0.001	0.003		04.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.45	.23	.00	240H-77F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00013.62	24H-70F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005419 5

06586 COATING 03-BL-51 POLYURETHANE FLAT BLUE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
		24H-150F-

80983 COATING 03-GY-62 FLAT LIGHT GRAY TOX RATE STUDY

MANF: DEFT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00012.43	24H-70F-ONE BRUSH COAT WAS APPLIED TO SUBSTRATE. LISTED RESULTS ARE AT 20 WEEKS. 24H-150F-

61878 COATING 03-GY-62 GRAY OVER MB0125-055 PRIMER GID: ATBGCQ

MANF: DEFT SPEC: MB0125-055
PRIMER/DESOTO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00010.65	SEE TEST REPORT

62059 COATING 03-GY-62 POLYURETHANE FLAT LIGHT GRAY GID: AKCQBG

MANF: DEFT SPEC: MIL-C-83286
DESOTO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.020	00.00	00.00	NONE
A	1	023.8	014.5	0.022	0.020	00.00	00.00	NONE
A	1	023.8	014.5	0.005	0.030	00.00	00.00	NONE
A	1	023.8	014.5	0.035		00.00	00.00	NONE
A	1	023.8	014.5	0.003	0.020	00.00	00.00	NONE
A	1	023.8	014.5	0.004	0.020	00.00	00.00	NONE
A	1	023.8	014.5	0.045		00.00	00.00	NONE
B	2	025.9	014.3	0.003	0.010	00.00	00.00	NONE
B	1	025.9	014.3	0.003	0.010		07.00	NONE
B	1	025.9	014.3	0.003	0.010	00.46	10.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.92	.40	.02	24H-46F- 24H-70F- 24H-150F- 24H-151F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00011.25	24H-150F-

05307 COATING 03-W-40 POLYURETHANE GLOSS WHITE GID: AKCQXX

MANF: DEFT SPEC: MIL-C-81773 MIL-C-83286

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.042	0.040	00.00	00.00	NONE
A	1	023.8	014.5	0.042	0.040	00.00	00.00	NONE
A	2	023.8	014.5	0.002	0.040	00.00	00.00	NONE
A	1	023.8	014.5	0.002	0.040	00.00	00.00	NONE
A	1	025.9	014.3	0.002	0.003		01.60	NONE
A	1	030.0	009.0	0.002	0.003		04.50	NONE
A	1	033.0	014.3	0.002			03.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.3E-6	1.86	.00		168H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00004.93	168H-70F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005420 1

05307 COATING 03-W-40 POLYURETHANE GLOSS WHITE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					24H-150F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
			24H-150F-

61855 COATING 03-Y-30 PRIMER GID: ATBGCQ

MANF: DEFT
PRIMER/DESOTO

SPEC: MB0125-055

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	B	00015.18	SEE TEST REPORT

05577 COATING 100PWB CONFIG GID: AKXXXX

....NO TEST DATA AVAILABLE....

20286 COATING 1295 EPOXY GID: AUBGXX

MANF: CASTALL INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	100.0	016.5	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	3.42	.00		24H-70F-
					24H-150F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	X	00000.53	24H-70F-
			24H-150F-

64889 COATING 17875 POLYURETHANE WHITE GID: AKCQXX

MANF: DESOTO

SPEC: MIL-C-83286

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		04.30	NONE
I	1	033.0	014.3	0.001	0.003	00.65	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	V	00014.68	

85384 COATING 2A53 EPOXY ON MULTIWIRE CIRCUIT BOARD

MANF:

SPEC: MIL-P-13949F

MIL-STD-105

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.093			00.50	NONE
A	1	025.9	014.3	0.053			00.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65365 COATING 33798 TOPCOAT WITH POLYAMIDE PRIMER GID: AUBGCD

MANF: RANDOLPH PRODUCTS

SPEC: MIL-C-83286

MIL-D-23377DT1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	015.0	0.002		00.28	08.00	NONE
I	1	025.9	014.3	0.002		00.42	12.00	T NONE
I	1	030.0	019.0	0.002		0.298	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20191 COATING 36231 ALKYD ENAMEL GID: ATAOXX

MANF: KOPPERS CO

SPEC: TT-E-527 COMP G

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		01.10	NONE
A	1	030.0	009.0	0.001	0.003		01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	X	00011.88	19.5H-70F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005421 3

00530 COATING 401 SERIES VELVET POLYESTER GID: ATCBXX

MANF: 3M CO SPEC: MB0125-019

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	009.0	0.005			12.00 T	SMALL
C	2	030.0	010.0	0.006	0.003		00.20	NONE
C	1	030.0	010.0	0.006	0.003	0.5	12.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00022.46	24H-150F-

05159 COATING 401-B2 GRAY GID: AUCBXX

MANF: 3M CO SPEC: MB0125-019
DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00024.46	24H-150F-

61450 COATING 401-C10 BLACK GID: ATCBXX

MANF: 3M CO SPEC: MB0125-019

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.50	.06	.35	168H-149F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00006.09	168H-70F- 24H-150F-

05160 COATING 401-F1 YELLOW

MANF: SPEC: MB0125-019

....NO TEST DATA AVAILABLE....

06624 COATING 421-03 GRAY GID: AUXXXX

MANF: FULLER O'BRIEN CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.004	0.062	00.00	00.00	NONE
A	1	030.0	010.0	0.004	0.062	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.9E-6	5.29	1.51	.16	8H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00007.82	8H-70F- 24H-150F-

61774 COATING 4367-3 ON LAMIN 515-700 GID: AKBHXX

MANF: DESOTO
PENNWALT CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00011.24	48H-70F-TWO COATS OF KOROPON WERE APPLIED WITH ONE HOUR INTERVAL BETWEEN APPLICATIONS. 24H-70F-TWO COATS OF LATEX PAINT 4367-3 WERE BRUSHED ON AT 90F WITH 2.0 HOUR INTERVAL BETWEEN APPLICATIONS.

60611 COATING 44 GM-7 AIRCRAFT GID: AUXYXX

MANF: DEFT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005422 5

60611 COATING 44 GM-7 AIRCRAFT (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		01.20	NONE
A	1	030.0	010.4	0.001	0.003		01.40	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.2E-6	5.04	.00	.00	24H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00003.79	24H-70F- 24H-150F-

TOXICITY

65207 COATING 44-GM-11 EPOXY POLYAMIDE GID: AUBGXX

MANF: DEFT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.0E-6	1.07	.29	.38	168H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

65376 COATING 44-GM-11/CHEMGLAZE A276 GID: AUXXXX

MANF: DEFT
LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	1.46	.21	.49	240H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60058 COATING 443-3-1 WHITE EPOXY GID: ATBGXX

MANF: BOSTIK FINCH

SPEC: 10A00528 1.7

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	10.00	.01	.00	168H-77F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60247 COATING 443-3-17 BLACK EPOXY GID: ATBGXX

MANF: BOSTIK FINCH

SPEC: 10A00528

....NO TEST DATA AVAILABLE....

06043 COATING 453-3-33 EPOXY GID: AKBGXX

....NO TEST DATA AVAILABLE....

85510 COATING 453-4-5/C212 POLYIMIDE EPOXY

MANF: BOSTIK FINCH

....NO TEST DATA AVAILABLE....

20242 COATING 453-4-BLUE POLYAMIDE SEMI-GLOSS EPOXY 212 GID: ATBLXX

MANF: BOSTIK FINCH

SPEC: MIL-C-22750T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		02.20	NONE
A	1	025.9	014.3	0.001	0.003		02.40	NONE
A	1	025.9	014.3	0.002	0.003		01.90	NONE
A	1	033.0	014.3	0.001	0.003		03.40	NONE
A	1	033.0	014.3	0.002	0.003		02.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.6E-6	4.75	.14		168H-70F- 24H-150F-

ODOR

RT	RT	WEIGHT	CURE
A	X	00004.85	168H-70F- 24H-150F-

TOXICITY

61138 COATING 463-12-19 EPOXY PRIMER GID: AKBGXX

MANF: BOSTIK FINCH

SPEC: MB0125-055

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.004			01.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005423 7

61364 COATING 463-12-19 PRIMER GID: AUBGXX

MANF: BOSTIK FINCH SPEC: MB0125-055

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.8E-6	5.21	.05		24H-70F- 24H-150F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	X	00006.05	24H-150F-

62411 COATING 463-12-8/643-1-1 EPOXY GID: AKXXXX

MANF: BOSTIK FINCH
VB 48H-1.0E5-200F

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.050	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.3E-6	1.33	.35	.34	48H-200F-0psia1E-5

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

60994 COATING 463-12-8/643-2-20 EPOXY GID: AUBGXX

MANF: BOSTIK FINCH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.2E-6	4.06	.25	.60	2H-70F-PMR2HRT TC14D68F 336H-68F-PMR2HRT TC14D68F

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

05688 COATING 463-12-8/C-116 EPOXY GID: AUBGXX

MANF: BOSTIK FINCH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62373 COATING 463-12-8/PRIMER GID: AUXXXX

MANF: BOSTIK FINCH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.29	.02	.00	2H-70F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

20452 COATING 463-3-100/C-118 PRIMER WHITE GID: AUBGXX

MANF: BOSTIK FINCH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002	0.003		02.10	NONE
A	1	033.0	014.3	0.002	0.003		04.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-7	3.52	.00		24H-70F- 24H-150F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	X	00009.75	24H-70F- 24H-150F-

62786 COATING 463-3-209 EPOXY GID: AKBGXX

MANF: BOSTIK FINCH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003	0.086	00.00	00.00	NONE
A	1	023.8	014.5	0.003	0.086	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60736 COATING 463-3-33 TC/515-700 PRIMER GID: ATBGXX

MANF: BOSTIK FINCH SPEC: STM0685-01
DESOTO

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005424 9

60736 COATING 463-3-33 TC/515-700 PRIMER (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.1E-6	.52	.04	.38	5856H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

06290 COATING 463-4-4 PRIMER EPOXY GID: AUBGXX

MANF: BOSTIK FINCH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001			02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.21	.00	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

60057 COATING 463-6-3 GREEN EPOXY GID: AUBGXX

MANF: BOSTIK FINCH SPEC: 10A00528 P1.6 16A10132

....NO TEST DATA AVAILABLE....

20169 COATING 463-6-5 PRIMER/463-3-8 EPOXY GID: ATBGXX

MANF: BOSTIK FINCH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		02.20	NONE
A	1	030.0	009.0	0.002			04.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.2E-6	8.12	.07	.30	24H-70F-
					24H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00007.44	SEE MFG

60337 COATING 463-7-26/A276/X-369 GID: ATXXXX

MANF: BOSTIK FINCH SPEC: MIL-C-83286 MIL-P-23377

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	X 00021.65	

62107 COATING 4699-121A/4334-109 GID: ATXXXX

MANF: PENNWALT CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	100.0	060.0	0.255			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05312 COATING 5078-5 CLEAR ENAMEL GID: ATAOAR

MANF: CARDINAL PAINT CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.005	0.003		00.20	NONE
C	1	023.8	014.5	0.005	0.003	00.69	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62135 COATING 513-703/821-331/910-736 GID: AKBGXX

MANF: DESOTO SPEC: MIL-C-83286T3 MIL-P-23377

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-7	2.73	.04		24H-70F-
					24H-160F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

62269 COATING 513X332/910X457 PRIMER GID: AUXXXX

MANF: DESOTO SPEC: MIL-P-23377

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005425 0

62269 COATING 513X332/910X457 PRIMER (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	2.6E-6	.84	.00		1H-70F- 12H-130F-

ODOR

RT	RT	WEIGHT	CURE
A	V	00009.16	1H-70F- 12H-130F-

TOXICITY

62134 COATING 515-700/910-704 463-3-100/118 GID: AKBGXX

MANF: DESOTO SPEC: STM 0685

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-7	5.71	.03		24H-70F- 24H-160F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

61424 COATING 515-700/910-704 CATALYST GID: AUBGXX

MANF: DESOTO SPEC: MB0125-055

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.003		04.90	SMALL
A	1	030.0	009.0	0.002	0.003		02.70	NONE
I	1	033.0	014.3	0.003	0.003	01.46	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

STM0685-01

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	500		70	0.001	0	20
B	MECH	500	72	70	0.001	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.91	.05	.00	24H-46F- 48H-250F-

ODOR

RT	RT	WEIGHT	CURE
	X	00012.71	24H-70F- 168H-70F-

TOXICITY

62558 COATING 515-703/910-736 PRIMER GID: AUBGCD

MANF: DESOTO SPEC: MIL-P-23377

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.75	.02	.39	5856H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60305 COATING 515X346 EPOXY GID: AUBGXX

MANF: DESOTO
FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

05892 COATING 519X303/020X324/910X357 GID: AKXXXX

....NO TEST DATA AVAILABLE....

60766 COATING 5205U PAINT WITH 8248 PRIMER GID: ATCQBG

MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.2E-6	.94	.02	.35	168H-70F- 24H-150F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00020.14	168H-70F- 24H-150F-

TOXICITY

60679 COATING 528-305/515-700 PRIMER GID: AMXXXX

MANF: DESOTO SPEC: STM0685-01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.4E-6	6.57	.00	.35	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05894 COATING 529-001/910-037/020-004 GID: ATXXXX

MANF: DESOTO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005426 2

05894 COATING 529-001/910-037/020-004 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.6E-6	9.42	.06		24H-70F-
					24H-70F-
					24H-150F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62778 COATING 550/5007/FOAM 658 POLYURETHANE GID: AKCQXX

MANF: FUTURA COATING INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	2.560			03.30	NONE
X	1	025.9	014.3	2.560		00.15	10.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06045 COATING 59-000 SERIES EPOXY GID: AKBGXX

....NO TEST DATA AVAILABLE....

06233 COATING 643-1-1 POLYURETHANE GID: ATCQXX

MANF: BOSTIK FINCH SPEC: MB0125-040

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.014		00.00	00.00	NONE
A	1	020.9	014.7	0.001	0.003	00.60	01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.42	.14	.00	24H-70F-
					12H-250F-0psiaVACUUM

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65158 COATING 643-18-1 WHITE GID: ATXXXX

MANF: SIKKENS SPEC: MIL-C-83286B

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.8E-6	1.25	.00	.47	168H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61345 COATING 6543U/PRIMER 8245 GID: ATCQBG

MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.4E-6	1.39	.10	.26	SEE TEST REPORT

ODOR

RT	RT WEIGHT	CURE
A	B 00019.15	SEE TEST REPORT

TOXICITY

60767 COATING 6561U PAINT WITH EPOXY PRIMER GID: ATCQBG

MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.2E-6	1.04	.05	.40	168H-70F-
					24H-150F-

ODOR

RT	RT WEIGHT	CURE
A	B 00019.08	168H-70F-
		24H-150F-

TOXICITY

05555 COATING 663-Z-20/C110 POLYURETHANE GID: AKCQXX

....NO TEST DATA AVAILABLE....

64247 COATING 6725-1 PRIMER GID: AUXXXX

MANF: NARMCO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.1E-6	19.12	2.31		24H-70F-

ODOR

RT	RT WEIGHT	CURE
	X 00000.50	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005427 4

05357 COATING 683-3-3Y POLYURETHANE GID: AKCQXX

MANF: BOSTIK FINCH SPEC: MIL-I-46058

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.004			00.90	NONE
C	1	023.8	014.5	0.004		00.90	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.1E-7	21.83	.03		168H-70F- 24H-150F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00005.63	168H-70F- 24H-150F-

64081 COATING 68U-1005/U3380 POLYURETHANE GID: AKXXXX

MANF: STERLING DIV OF REICHHOLD CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.4E-6	8.98	.05	.39	24H-70F- 2H-150F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05720 COATING 7312-A01F GRAY POLYURETHANE GID: AKXXXX

MANF: SPEC: MIL-C-81773

....NO TEST DATA AVAILABLE....

61668 COATING 7414/PRIMER EPOXY 8245 GID: ATCQBG

MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.4E-6	1.52	.05	.28	SEE TEST REPORT

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00019.73	SEE TEST REPORT

06289 COATING 7X983 SILICONE 3709-A13 GID: AKXXXX

MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05201 COATING 821-331 POLYURETHANE FLAT WHITE GID: ATCQXX

MANF: DESOTO SPEC: MIL-C-83286 STM 0685

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.024	0.020		00.80	NONE
A	1	023.8	014.5	0.022	0.020		00.50	NONE
X	2	025.9	014.3	0.003			04.20	NONE
X	1	025.9	014.3	0.003		04.00	06.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.2E-6	.34	.01		24H-150F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00002.30	17520H-70F-

61471 COATING 821-331 POLYURETHANE FLAT WHITE GID: ATCQXX

MANF: DESOTO SPEC: MIL-C-83286

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.005			07.50	NONE
B	1	025.9	014.3	0.005			08.50	NONE
A	1	025.9	014.3	0.020	0.003	00.00	00.00	NONE
B	1	030.0	009.0	0.005			08.00	NONE
A	1	033.0	014.3	0.020	0.003	00.00	00.00	NONE
A	1	100.0	020.2	0.020	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.6E-6	2.85	.00		2H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00018.65	2H-70F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005428 6

61471 COATING 821-331 POLYURETHANE FLAT WHITE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					168H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
		2H-150F-

60680 COATING 821-331 POLYURETHANE FLAT WHITE WITH PRIMER GID: ATBGCQ

MANF: DESOTO SPEC: MIL-C-83286 MIL-P-23377

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.1E-6	.72	.02	.66	5856H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

61470 COATING 821-400 POLYURETHANE GLOSS WHITE GID: ATCQXX

MANF: DESOTO SPEC: MIL-C-83286

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.046	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.046	0.003	00.00	00.00	NONE
A	1	100.0	020.2	0.046	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.6E-6	1.22	.01		2H-70F-
					2H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00019.25	2H-70F-
		2H-150F-

63765 COATING 821-425/515-700 PRIMER GID: AKXXXX

MANF: DESOTO SPEC: MIL-C-83286 STM 0685

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	6.35	

61592 COATING 822-326 PRIMER GID: AUBGCQ

MANF: DESOTO SPEC: MB0125-055

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00006.68	180H-70F-
		48H-150F-

61854 COATING 822-327 GRAY 36231 OVER MB0125-055 PRIMER GID: ATBGCQ

MANF: DESOTO SPEC: MB0125-055

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00008.16	SEE TEST REPORT

05983 COATING 822-327 POLYURETHANE FLAT GRAY GID: AKCQXX

MANF: DESOTO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	009.0	0.006	0.003	00.94	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05404 COATING 822-327 POLYURETHANE FLAT LT GRAY GID: ATCQXX

MANF: DESOTO SPEC: MIL-C-83286

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.020	00.00	00.00	NONE
A	1	023.8	014.5	0.005	0.030	00.00	00.00	NONE
A	1	023.8	014.5	0.022	0.002	00.00	00.00	NONE
C	2	025.9	014.3	0.001	0.010	00.00	00.00	NONE
C	1	025.9	014.3	0.001	0.010		07.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005429 8

05404 COATING 822-327 POLYURETHANE FLAT LT GRAY (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.002	0.020		00.50	NONE
A	1	030.0	009.0	0.003	0.010		01.90	NONE
B	1	033.0	014.3	0.001			08.40	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.55	.90	.00	24H-70F- 24H-150F-

ODOR

RT	RT	WEIGHT	CURE
A	V	00010.24	24H-70F-25.9% OXYGEN 24H-150F-

TOXICITY

05403 COATING 823-311 POLYURETHANE FLUOREL/YELLOW GID: AKCQXX

MANF: DESOTO SPEC: MIL-C-83286T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.022			00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.4E-6	3.14	.05	.54	

ODOR

RT	RT	WEIGHT	CURE
A	B	00009.50	168H-70F-

TOXICITY

61853 COATING 823-311 PRIMER GID: ATBGCQ

MANF: DESOTO SPEC: MB0125-055

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	X	00017.22	SEE TEST REPORT

TOXICITY

63973 COATING 823-363 POLYURETHANE GLOSS ORANGE GID: ATCRXX

MANF: DESOTO SPEC: MIL-C-83286

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001			00.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.7E-6	3.27	.03		

ODOR

RT	RT	WEIGHT	CURE
A	B	00003.60	24H-150F-

TOXICITY

64975 COATING 824-408 POLYURETHANE GLOSS ORANGE GID: ATCRXX

MANF: DESOTO SPEC: MIL-C-83286

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.8	014.3	0.001	0.003	00.75	12.00 T	NONE
A	1	025.9	014.3	0.002	0.020	00.00	00.00	NONE
A	1	033.2	015.6	0.002	0.020	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

80979 COATING 828-310 FLAT BLACK TOX RATE STUDY

MANF: DESOTO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	V	00014.50	

TOXICITY

05402 COATING 828-310 POLYURETHANE FLAT BLACK GID: AKCQXX

MANF: DESOTO SPEC: MIL-C-83286

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005	0.030	00.00	00.00	NONE
B	1	030.0	009.0	0.002		00.45	07.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.3E-6	1.17	.03		168H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005430 4

05402 COATING 828-310 POLYURETHANE FLAT BLACK (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					24H-257F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE

61852 COATING 828-310 PRIMER GID: ATBGCQ

MANF: DESOTO SPEC: MB0125-055

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00007.77	SEE TEST REPORT

05932 COATING 850-204 TFE GREEN GID: AKCNXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	72	200	0.003	0	20
B	PNEU	400		70	0.003	0	20
B	MECH	400	72	70	0.003	0	20
B	MECH	600	72	-297	0.064	0	20

80088 COATING 850-204/851-214 GREEN

MANF: DUPONT SPEC: ME261-0045

....NO TEST DATA AVAILABLE....

61287 COATING 850-204/851-225/856-204 GID: AKCNXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	-297	0.003	0	20
B	MECH	15	72	-297	0.003	0	20
I	PNEU	2000		70	0.003	0	04
I	PNEU	4000		70	0.003	0	04
I	PNEU	5000		70	0.003	0	03
B	PNEU	6000		70	0.003	0	20
I	PNEU	6000		70	0.003	0	20

61883 COATING 850-204/851-245/856-204 GID: AKBOCN

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	600	72			0	20

62897 COATING 850-204/855-225 TFE GID: AKCOXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.005	0	20

06050 COATING 851-204 TEFLON PRIMER GID: ATXXXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1050		120	0.002	0	20
B	MECH	1250	72	120	0.001	0	20
B	PNEU	1250		120	0.002	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005431 6 ■

06030 COATING 851-204/851-224 TFE GID: AKEFXX

MANF: DUPONT

FLAMMABILITY								FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	PNEU	260.0		350	0.001	0	20
											B	PNEU	285.0		200	0.001	0	20
											B	MECH	14.7	72	-297	0.003	0	20
											B	PNEU	260		350	0.001	0	20
											B	MECH	260	72	350	0.001	0	20
											B	PNEU	285		200	0.001	0	20
											B	MECH	285	72	200	0.001	0	20
											B	PNEU	45		500	0.001	0	20
											B	MECH	45	72	500	0.001	0	20

06287 COATING 851-224 GREEN/850-204 GREEN GID: AKCNXX

MANF: DUPONT SPEC: MC284-0391

FLAMMABILITY								FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	PNEU	3300		150	0.065	0	20
											B	MECH	3300	72	150	0.065	0	20
											B	MECH	400	72	-297	0.065	0	20
											B	MECH	675	72	540	0.077	0	20

06034 COATING 851-225 BLK/850-201 GID: ATXXXX

MANF: DUPONT SPEC: AMS 2515

FLAMMABILITY								FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	1050	72	-297	0.002	0	20
											B	PNEU	1500		350	0.002	0	20
											X	PNEU	2000		350	0.002	3	07
											X	PNEU	3000		350	0.002	2	04
											X	PNEU	4000		350	0.002	4	04
											B	MECH	5000	72	350	0.002	0	20

05944 COATING 851-245 TOPCOAT/850-204 PRIMER GID: ATXXXX

MANF: DUPONT

FLAMMABILITY								FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	1000	72	-297	0.065	0	20
											B	PNEU	1000		200	0.002	0	20
											B	MECH	1000	72	200	0.065	0	20
											B	MECH	600	72	450	0.065	1	60

62825 COATING 851-255 BLACK/850-204 TFE GID: AUXXXX

MANF: SIERRACIN/HARRISON

FLAMMABILITY								FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	600	72	450	0.002	0	20

65555 COATING 856-204 TFE GREEN/851-255 TFE BLACK/850-204 TFE GREEN PRIMER GID: AKXXXX

MANF: DUPONT

FLAMMABILITY								FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	600	72	400		00	20

06029 COATING 856-204/855-225/850-204 GID: ATXXXX

MANF: DUPONT SPEC: MMC P/N 55LC

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005432 8

06029 COATING 856-204/855-225/850-204 (cont)

MANF: MEGATECH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.065	0	20
B	MECH	275	72	-297	0.068	0	20
B	MECH	275	72	350	0.065	0	20
B	MECH	600	72	-297	0.063	0	20
B	MECH	600	72	450	0.063	0	20

06508 COATING 856-301/FEP PR 856-204 TOPCOAT GID: AKBOXX

....NO TEST DATA AVAILABLE....

06337 COATING 958-203 TEFLON GID: AKCNXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.003		01.50	NONE
A	1	030.0	009.0	0.003	0.003		01.50	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	150	0.065	0	20
B	MECH	500	72	150	0.065	0	20

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.40	

06189 COATING 959-203 TFE BLACK GID: AKCNXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002	0.010	00.00	00.00	NONE
A	1	033.0	014.3	0.002		00.00	00.00	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	9.0E-7	6.76	.10		.16H-70F- .25H-300F- .25H-650F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	0.92	SEE MFG

05169 COATING 96-005 SILICONE GID: ALCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005	0.003		01.80	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.4E-7	1.25	.62		168H-70F- 24H-150F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70		1	02
X	PNEU	1500		70		1	01
I	PNEU	500		70		0	20

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00001.47	24H-70F-

61258 COATING A136 EPOXY GID: AKBGXX

MANF: ANDREW BROWN
KOPPERS CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.010	0.062	00.00	00.00	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.4E-6	1.09	.11		4H-46F- 25H-250F-0psia1E-4 TORR

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005433 T

61258 COATING A136 EPOXY (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					1H-250F-
					24H-250F-0psiaVACUUM

ODOR

RT	RT WEIGHT	CURE

TOXICITY

60974 COATING A1716/BT1-1 GID: AKXXXX

MANF: KOPPERS CO SPEC: MIL-P-23377

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.2E-6	3.78	.58	.10	24H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

80059 COATING A276 WITH PGEA/515700/910704 GID: AKXXXX

MANF: LORD CORP SPEC: 9M03235-1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	2.91	.02	.36	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64897 COATING A276/02-Y-24 GID: AUXXXX

MANF: DEFT SPEC: MIL-C-83286 MIL-P-23377

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.27	.00	.13	4H-302F-

ODOR

RT	RT WEIGHT	CURE
A	00020.24	

TOXICITY

64898 COATING A276/P527D GID: AUXXXX

MANF: KOPPERS SPEC: MIL-C-83286 MIL-P-23377

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.46	.10	.00	168H-77F-
					16H-185F-

ODOR

RT	RT WEIGHT	CURE
A	00020.06	

TOXICITY

06069 COATING A4094 SILICONE GID: AUCKXX

....NO TEST DATA AVAILABLE....

02055 COATING A423/T252 EPOXY GID: AKBGXX

MANF: ANDREW BROWN SPEC: MB0125-033

....NO TEST DATA AVAILABLE....

05071 COATING A934BX AMINO SILANE GID: AUARXX

MANF: B F GOODRICH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	PNEU	1500			0.001	0	20
I	MECH	1500	72	70	0.001	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.8E-7	61.98	.01		24H-150F-

ODOR

RT	RT WEIGHT	CURE
A	X 00000.03	24H-149F-

TOXICITY

60356 COATING ACCUMETRIC A105 GID: AUXXXX

MANF: DETREX CHEMICAL SPEC: LAC40-4394

....NO TEST DATA AVAILABLE....

20463 COATING ACETATE BUTYRATE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.73	.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005434 1

62209 COATING ACRYLIC 3715-51-2B A-601 GID: ATAKXX

MANF: PENNWALT CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		01.80	NONE
A	1	100.0	014.5	0.016	0.250	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.9E-6	2.94	.10		24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00004.19	24H-70F-

62210 COATING ACRYLIC 3715-52-1 GID: ATAKXX

MANF: PENNWALT CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		01.50	NONE
A	1	100.0	014.5	0.014	0.250	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.9E-6	1.25	.04		24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00006.91	24H-70F-

62422 COATING ACRYLIC 90-10472 CORROSION PREVENTIVE GID: ALAKXX

MANF: STERLING DIV OF REICHHOLD CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.4E-6	6.98	.00	.36	72H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

64080 COATING ACRYLIC CLEAR 90-10530

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.2E-6	8.88	.01	.34	24H-70F-
					24H-150F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

06437 COATING ACRYLIC E28A GID: AKAKXX

....NO TEST DATA AVAILABLE....

60081 COATING ACRYLIC EMUL-EXT-WHITE

MANF:

SPEC: TT-P-19

....NO TEST DATA AVAILABLE....

60224 COATING ACRYLIC ENAMEL GID: AKAKXX

....NO TEST DATA AVAILABLE....

61211 COATING ACRYLIC ENAMEL BLACK GID: ATAKXX

MANF: SHERWIN WILLIAMS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00005.52	2H-200F-

20040 COATING ACRYLIC ENAMEL SW CLEAR GID: ATXXXX

MANF: SHERWIN WILLIAMS

....NO TEST DATA AVAILABLE....

20038 COATING ACRYLIC ENAMEL SW J5-5226 GID: ATAKXX

MANF: SHERWIN WILLIAMS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE
V	00007.81	2H-200F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005435 3

20039 COATING ACRYLIC ENAMEL SWF1081738 GID: ATAKXX

....NO TEST DATA AVAILABLE....

60726 COATING ACRYLIC PC20/20M GID: COAKXX

MANF: HYSOL/DEXTER SPEC: BURNDY ML120T-6

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.075		00.10	12.00	NONE
A	1	025.9	014.3	0.400			01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.00	.05	.00	70H-257F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00011.76	7H-167F-

60262 COATING ADHESIVE POLYSTYRENE GID: AKXXXX

....NO TEST DATA AVAILABLE....

20422 COATING AERO-CATICOAT GID: AKXXXX

....NO TEST DATA AVAILABLE....

65009 COATING AEROCOAT AR7 SEE REPORT GID: ATXXXX

MANF: B F GOODRICH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
X	HYZE
X	MMH
X	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06338 COATING AEROSEAL CERAMIC (INORG) GID: AKIAXX

....NO TEST DATA AVAILABLE....

20170 COATING ALKYD GLOSS ENAMEL 12246 GID: ATXXXX

MANF: CHEMRAY COATINGS SPEC: TT-E-489 TT-E-489CA
KOPPERS CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.001	0.003		00.10	NONE
A	1	020.9	014.7	0.001	0.003		01.70	NONE
X	2	025.9	014.3	0.001	0.003		00.10	NONE
X	1	025.9	014.3	0.002	0.003	01.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.4E-6	7.09	.57	.20	10H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00012.43	8H-70F-

06461 COATING ALKYD GLOSS ENAMEL YELLOW GID: ATAPXX

MANF: AQM SPEC: TT-E-489

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-6	.95	.00	.91	24H-70F-
					48H-350F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

64026 COATING ALKYD-MELAMINE ENAMEL GID: ATXXXX

MANF: ATMOSPHERIC SERVICES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00813.27	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005436 5

65025 COATING ALUMINIZED ENAMEL SEE REPORT GID: APXXXX

MANF: KOPPERS CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
S					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05775 COATING ANTIREFLECTIVE INORGANIC GID: AKXXXX

....NO TEST DATA AVAILABLE....

20553 COATING APCO 434/SONITE 41 EPOXY GID: AKBGXX

MANF: HAMILTON STANDARD SPEC: SVHS 8091T5

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.104	0.003	00.00	00.00	NONE
A	1	100.0	020.2	0.104	0.003		00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.03	.00		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.13	

64138 COATING AR7 ON CRES 304 GID: AKXXXX

MANF: B F GOODRICH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
S		020.9						NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65065 COATING AR7 ON KEL-F DISCS GID: AKXXXX

MANF: B F GOODRICH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.001	1	4
X	MECH	14.7	72	-297	0.060	1	02
B	PNEU	1500		70	0.060	0	20
X	PNEU	2000		70	0.001	1	20
X	PNEU	2500		70	0.001	2	4
X	MECH	4000	72	70	0.010	2	02
X	MECH	4000	72	70	0.060	2	02

65119 COATING AR7 ON STEEL DISCS GID: AKFJXX

MANF: B F GOODRICH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.006	1	01
B	PNEU	1500		70	0.010	0	20
B	PNEU	2000		70	0.001	0	20
X	PNEU	2500		70	0.010	1	09
C	MECH	4000	30	30	0.001	0	20
C	MECH	4000	45	70	0.001	0	20
X	MECH	4000	10	-297	0.004	01	04
C	MECH	4000	20	-297	0.010	0	20

65067 COATING AR7 ON TEFLON TFE DISCS GID: AKCOXX

MANF: B F GOODRICH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000.0		70	0.060	00	20
C	MECH	14.7	35	-297	0.060	0	20
X	MECH	14.7	20	-297	0.060	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005437 7

65067 COATING AR7 ON TEFLON TFE DISCS (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	2500.0		70	0.060	01	03
X	PNEU	3000.0		70	0.060	01	02
X	MECH	4000	10	-297	0.004	01	04
B	MECH	4000	10	-297	0.060	01	03
X	MECH	4000	10	70	0.060	00	20

65063 COATING AR7 WITH KRYTOX 240AC GID: AKXXXX

MANF: B F GOODRICH
DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.010	1	04
B	PNEU	2000		70	0.010	00	20
X	PNEU	2500		70	0.010	01	01
X	PNEU	3000		70	0.010	01	10
C	MECH	4000	45	-297	0.010	00	20
B	MECH	4000	72	70	0.010	0	20
X	PNEU	4000		70	0.010	01	06

61731 COATING ARMAFLEX VINYL GID: AKCUXX

MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.5				01.30	NONE
A	1	023.8	014.5	0.001		00.00	00.00	NONE
I	1	024.5	014.5			00.13	12.00	T NONE

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00001.50	168H-70F-

20423 COATING ASTRODYNE 922 GID: AKXXXX

....NO TEST DATA AVAILABLE....

60714 COATING BARRY CONTROLS 103 GID: AKXXXX

MANF: BARRY WRIGHT CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	1.78	.60		

ODOR

RT

No test data

TOXICITY

RT	WEIGHT	CURE

05448 COATING BERYLCOAT D (INORGANIC) GID: AKXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025		00.00	00.00	NONE
A	1	023.8	014.7	0.025		00.00	00.00	NONE
A	1	024.5	014.7	0.025		00.00	00.00	NONE
A	1	025.9	014.7	0.025		00.00	00.00	NONE
A	1	030.0	014.7	0.025		00.00	00.00	NONE
A	1	100.0	014.7	0.025		00.00	00.00	NONE

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE

06125 COATING BISPHENOL A EPOXY FLDIZE GID: AKBGXX

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005438 9

85453 COATING BLACK 37038 POLYAMIDE EPOXY

MANF: TEMPO PAINT AND VARNISH — SPEC: MIL-C-22750C1T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		02.40	NONE
A	1	033.0	014.3	0.001	0.003		03.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.80	.24		2.5H-140F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	X 00009.74	2.5H-140F-

05908 COATING BLACK ENAMEL/ZNCRO4 GID: AKXXXX

....NO TEST DATA AVAILABLE....

20132 COATING BLACK OXIDE (INORGANIC) GID: AKXXXX

MANF: — SPEC: MIL-C-13924C1

....NO TEST DATA AVAILABLE....

05384 COATING BR 127 EPOXY GID: AUXXXX

MANF: AMERICAN CYANAMID — SPEC: MB0120-078T4

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.001	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.001	0.003		01.80	NONE
A	1	030.0	009.0	0.004			02.60	NONE
A	1	100.0	019.0	0.001	0.010	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.48	.03	.00	1.5H-261F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	X 00003.97	168H-70F- 24H-150F-

61006 COATING BROMA 101 CLEAR ACRYLIC GID: ATAKXX

MANF: MASTER BRONZE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.10	1.07	.00	16H-70F- .25H-250F-

ODOR

RT	RT WEIGHT	CURE
A	X 00000.84	24H-150F-

TOXICITY

60360 COATING BSL 112 PRIMER GID: AUXXXX

MANF: CIBA-GEIGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.64	.08	.00	.58H-248F-0psiaVACUUM

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06044 COATING C12546 EPOXY GID: AKXXXX

MANF: UNI-GLAZE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.002	0.003		03.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	10.52	.01	.29	1H-75F-12.4psia .33H-250F-12.4psia

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	22.153	1H-75F-12.4psia .33H-250F-12.4psia

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005439 0

05751 COATING C7-23/C10-32 GID: AKXXXX

....NO TEST DATA AVAILABLE....

80154 COATING CAMIE 2000 ACRYLIC SPRAY

....NO TEST DATA AVAILABLE....

65000 COATING CARBOLINE NO 10 SEE RPT GID: ATXXXX

MANF: CARBOLINE

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N2O4							

65001 COATING CARBOLINE NO 11 SEE RPT GID: ATXXXX

MANF: CARBOLINE

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N2O4							

65002 COATING CARBOLINE NO 12 SEE RPT GID: ATXXXX

MANF: CARBOLINE

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									A	HYZE	No test data						
									X	MMH							
									X	N2O4							

65003 COATING CARBOLINE NO 13 SEE RPT GID: ATXXXX

MANF: CARBOLINE

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N2O4							

65004 COATING CARBOLINE NO 14 SEE RPT GID: ATXXXX

MANF: CARBOLINE

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									A	HYZE	No test data						
									X	MMH							
									X	N2O4							

65005 COATING CARBOLINE NO 15 SEE RPT GID: ATXXXX

MANF: CARBOLINE

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N2O4							

65006 COATING CARBOLINE NO 16 SEE RPT GID: ATXXXX

MANF: CARBOLINE

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005440 7

65006 COATING CARBOLINE NO 16 SEE RPT (cont)

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
									X	MMH							
									X	N204							

65007 COATING CARBOLINE NO 17 SEE RPT GID: ATXXXX
MANF: CARBOLINE

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

65008 COATING CARBOLINE NO 18 SEE RPT GID: ATXXXX
MANF: CARBOLINE

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

65019 COATING CARBOLINE NO 30 SEE RPT GID: ATXXXX
MANF: CARBOLINE
PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

65020 COATING CARBOLINE NO 31 SEE RPT GID: ATXXXX
MANF: CARBOLINE

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

65021 COATING CARBOLINE NO 32 SEE RPT GID: ATXXXX
MANF: CARBOLINE

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

65032 COATING CARBOLINE NO 33 SEE RPT GID: ATXXXX
MANF: CARBOLINE

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

20217 COATING CAT-A-LAC 443-3-6
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005441 9 ■

61604 COATING CAT-A-LAC 463-3-8/C118 GID: ATBGXX

MANF: BOSTIK FINCH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.007	0.062	00.00	00.00	NONE
A	1	033.0	014.3	0.007	0.062	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.38	.23	.00	24H-300F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00019.92	192H-70F- 24H-150F-

60352 COATING CHEMGLAZE 9922 A/B GID: AUBGXX

MANF: LORD CORP SPEC: HUG-LAC37-4462

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.001		05.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	2.49	.01	1.90	168H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

06177 COATING CHEMGLAZE 9924 A/B GID: AUCUXX

MANF: LORD CORP SPEC: MBO125-084 ST47P089

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		00.80	NONE
A	1	025.9	014.3	0.001	0.003		01.20	NONE
A	1	030.0	010.4	0.001	0.003		00.90	NONE
A	1	033.0	014.3	0.001	0.003		01.20	NONE
C	1	100.0	020.2	0.001	0.003	01.13	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	3.04	.09	.75	.25H-70F- 2H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00002.77	1H-70F-ONE BRUSH COAT WAS APPLIED. 24H-70F-A SECOND COAT WAS APPLIED OVER THE FIRST CURED COAT. 24H-150F-

20750 COATING CHEMGLAZE A170 GID: AKXXXX

MANF: LORD CORP

....NO TEST DATA AVAILABLE....

65553 COATING CHEMGLAZE A276/02-GN-40 PRIMER GID: AKXXXX

MANF: DEFT SPEC: SP-R-0022A
LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	1.39	.09	.32	4H-200F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

65445 COATING CHEMGLAZE A276/9924 PRIMER GID: ATXXXX

MANF: LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.26	.14		24H-70F-MIX RATIO 50 PARTS A276 TO 50 PARTS 9924

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

65449 COATING CHEMGLAZE A276/KOROPON GID: ATXXXX

MANF: DESOTO
LORD CORP

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005442 0

65449 COATING CHEMGLAZE A276/KOROPON (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	0.005		00.38	12.00	T NONE
I	1	024.5	014.5	0.004		00.62	12.00	T NONE
I	1	024.5	014.5	0.003		01.26	12.00	T NONE
I	1	024.5	014.5	0.006		00.30	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	3.35	.13	.38	24H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

81083 COATING CHEMGLAZE A276/PYROLAC 123

MANF: LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.06	.04	2.44	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63761 COATING CHEMGLAZE A471 POLYURETHANE GRAY GID: ATCQXX

MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001		00.26	01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80145 COATING CHEMGLAZE A571 RED

MANF: LORD CORP

....NO TEST DATA AVAILABLE....

62270 COATING CHEMGLAZE A571 RED/9924 GID: AKXXXX

MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.001	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.001	0.003	00.85	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.2E-6	2.04	.01	.36	24H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
A	B 00010.89	24H-70F- 24H-150F-

TOXICITY

80146 COATING CHEMGLAZE A671 LIGHT GREEN

MANF: LORD CORP

....NO TEST DATA AVAILABLE....

80147 COATING CHEMGLAZE A871 ORANGE

MANF: LORD CORP

....NO TEST DATA AVAILABLE....

80148 COATING CHEMGLAZE A971 YELLOW

MANF: LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.29	.09	.00	168H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

81081 COATING CHEMGLAZE H322/LESONAL PRIMER

MANF: LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.37	.00	.10	.25H-257F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005443 2

81081 COATING CHEMGLAZE H322/LESONAL PRIMER (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.08	.00	2.32	24H-212F- 46F- 24H-212F- .5H-122F- .25H-257F- 30H-257F- 50H-212F-

ODOR / TOXICITY: No test data

06236 COATING CHEMGLAZE II A276 GID: AKCQXX

MANF: LORD CORP SPEC: MB0125-080

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.025		00.00	00.00	NONE
A	1	020.9	014.7	0.025		00.00	00.00	NONE
C	2	025.9	014.3	0.003		00.00	00.00	NONE
C	1	025.9	014.3	0.003		00.83	12.00	T NONE
C	2	030.0	010.0	0.003	0.003	00.01	00.10	NONE
C	1	030.0	010.0	0.003	0.003	00.08	12.00	T NONE

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.52	.04	.00	.5H-158F- 1H-347F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00019.80	24H-70F- 72H-70F- 24H-150F-

62765 COATING CHEMGLAZE II A276/9922 PRIMER GID: AKBGXX

MANF: LORD CORP SPEC: LAC37-4462D SP-R-0022A LAC37-4467A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.006	0.001	00.00	00.00	NONE
B	1	020.9	014.7	0.006	0.001	02.06	09.50	NONE

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.0E-6	.99	.15	.28	4H-200F-

ODOR / TOXICITY: No test data

64986 COATING CHEMGLAZE II A471 GID: AKXXXX

MANF: WIEDERHOLD

....NO TEST DATA AVAILABLE....

81082 COATING CHEMGLAZE L300

MANF: LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.40	.06	1.49	

ODOR / TOXICITY: No test data

81084 COATING CHEMGLAZE L300/PYROLAC 123

MANF: LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.20	.03	2.84	24H-46F- 16H-64F-

ODOR / TOXICITY: No test data

62331 COATING CHEMGLAZE V021/9992 GID: AKXXXX

MANF: LORD CORP

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005444 4

62331 COATING CHEMGLAZE V021/9992 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	025.0	0.001	0.003	00.63	12.00	T MOD
X	1	100.0	025.0	0.001	0.003	03.37	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.3E-6	6.54	1.19	.43	.08H-173F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00016.08	.08H-173F-

TOXICITY

62333 COATING CHEMGLAZE V021/9995 GID: AKXXXX

MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	025.0	0.002	0.003	00.65	12.00	T NONE
X	1	100.0	025.0	0.002	0.003	03.35	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.5E-6	9.77	1.40	.49	.08H-173F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00020.36	.08H-173F-

TOXICITY

62332 COATING CHEMGLAZE V021/XYLENE GID: AKXXXX

MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	025.0	0.001	0.003	00.54	12.00	T NONE
X	1	100.0	025.0	0.001	0.003	02.76	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.5E-6	3.74	.79	.44	.08H-173F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00013.31	.08H-173F-

TOXICITY

06214 COATING CHEMGLAZE Z202 POLYURETHANE GID: ATCQXX

MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.002	0.003	00.00	00.00	NONE
C	1	020.9	014.7	0.002	0.003	00.38	12.00	T NONE
A	1	023.8	014.5	0.002	0.003		04.30	NONE
C	2	025.9	014.3	0.003	0.003		00.30	NONE
C	1	025.9	014.3	0.003	0.003	00.50	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.61	.02	.00	168H-77F-

ODOR

RT	RT	WEIGHT	CURE
	V	00020.10	24H-70F-
			168H-70F-
			8H-150F-

TOXICITY

65552 COATING CHEMGLAZE Z302 GID: AKXXXX

MANF: LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.39	.01	.00	336H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

65539 COATING CHEMGLAZE Z302/02-GN-40PRIMER GID: AKXXXX

MANF: DEFT
LORD CORP

SPEC: SP-R-0022A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	2.57	.03	.44	4H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005445 6

65537 COATING CHEMGLAZE Z302/9922 PRIMER GID: AKXXXX

MANF: LORD CORP SPEC: SP-R-0022A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	5.0E-6	1.35	.05	.49	4H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65538 COATING CHEMGLAZE Z302/9924 PRIMER GID: AKXXXX

MANF: LORD CORP SPEC: SP-R-0022A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	2.89	.16	.71	4H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06173 COATING CHEMGLAZE Z306 GID: ATCQXX

MANF: LORD CORP SPEC: MIL-P-23377 MMC/STM K794

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002		00.00	00.00	NONE
A	1	020.9	014.7	0.001	0.003		02.70	NONE
A	1	020.9	014.7	0.030	0.003	00.00	00.00	NONE
B	2	025.9	014.3	0.002	0.003		00.10	NONE
B	1	025.9	014.3	0.002	0.003		06.20	NONE
A	1	025.9	014.3	0.001			03.40	NONE
A	1	030.0	009.0	0.002	0.115	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.0E-6	.91	.00		24H-70F-
					168H-70F-
					24H-150F-

ODOR

RT	RT WEIGHT	CURE
A	B 00009.40	24H-70F-
		168H-70F-
		24H-150F-

TOXICITY

65542 COATING CHEMGLAZE Z306/02-GN-40 PRIMER GID: AKXXXX

MANF: DEFT
LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	4.35	.55	.27	4H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65540 COATING CHEMGLAZE Z306/9922 PRIMER GID: AKXXXX

MANF: LORD CORP SPEC: SP-R-0022A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.55	.02	.45	16H-46F-
					16H-140F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65097 COATING CHEMGLAZE Z306/9924 GID: AKXXXX

MANF: LORD CORP SPEC: MMC-STP-30151 SP-R-0022A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.070	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.18	.05	.00	504H-70F-
					24H-212F-0psiaVACUUM

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61864 COATING CHEMGLAZE Z306/AP131 GID: ATCQXX

MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005446 8

61864 COATING CHEMGLAZE Z306/AP131 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003	00.00	00.00	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.76	.05		720H-77F-

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

81080 COATING CHEMGLAZE Z306/PYROLAC 123

MANF: LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.63	.06	.00	2H-46F-
					16H-140F-
					12H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20748 COATING CHEMGLAZE Z651 POLYURETHANE 9924 GID: ATXXXX

MANF: LORD CORP
XCA/PR1-XAA/PR2-XFA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.005	0.003		00.20	NONE
C	1	025.9	014.3	0.005	0.003	00.52	12.00 T	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.35	.03	.00	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
X	X 00020.31	1H-70F-
		4H-70F-
		168H-70F-

TOXICITY

20747 COATING CHEMGLAZE Z752 POLYURETHANE 9924 GID: ATXXXX

MANF: LORD CORP
XEA/PR1-XAA/PR2-XFA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.005	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.005	0.003	00.68	12.00 T	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	5.0E-6	4.58	.00		1H-70F-
					168H-70F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
A	V 00020.08	1H-70F-
		4H-70F-
		168H-70F-

TOXICITY

20746 COATING CHEMGLAZE Z853/9986 GID: AKCQXX

MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.002	0.003	00.00	00.00	NONE
B	1	025.9	014.3	0.002	0.003		07.80	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.45	.03	.00	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
A	B 00019.88	1H-70F-
		4H-70F-
		168H-70F-

TOXICITY

62439 COATING CHOCKFAST ORANGE PR610 TCF GID: AKBGXX

MANF: PHILADELPHIA RESINS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME
A	HYZE

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005447 T

62439 COATING CHOCKFAST ORANGE PR610 TCF (cont)

FSC

RT	FLUID NAME
X	HYZE
X	MMH
X	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

80084 COATING CHOSHIELD 596 A/B EPOXY

MANF: CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.003	0.003		04.20	NONE

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY: No test data

ODOR: No test data

TOXICITY

RT	WEIGHT	CURE
X	20.880	48H-70F-

06616 COATING CHOSHIELD EPOXY/AG FILLD GID: AKBGCQ

MANF: CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002	0.030		01.60	NONE

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.5E-6	.41	.00	.37	1H-70F- 3H-350F-

ODOR: No test data

TOXICITY: No test data

05933 COATING CONAPOXY 1122 GID: AKBGXX

MANF: CONAP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003		04.20	NONE

FSC: No test data

OXYGEN COMP: No test data

80069 COATING CONATHANE EN2 POLYURETHANE

MANF: CONAP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.0E-6	.80	.06	.23	1H-199F-

ODOR: No test data

TOXICITY

05784 COATING CONATHANE EN4 (DPEN6385) GID: BACQXX

MANF: CONAP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.016		00.00	00.00	NONE
A	1	023.8	014.5	0.016			02.30	NONE
I	1	030.0	010.0	0.016		00.50	12.00	T SMALL

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.15	.49	.00	24H-176F-

ODOR

RT	RT	WEIGHT	CURE
A	X	00015.61	16H-150F-

TOXICITY

61153 COATING CONDUCTIVE 463-6-14 GID: ATBGXX

MANF: BOSTIK FINCH SPEC: BMS10-21C TY1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.98	.35	.00	25H-77F- 1H-150F-

ODOR: No test data

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005448 1

64278 COATING CONDUCTIVE INK #703-5-1 GID: AKXXXX

MANF: SHELDAHL SPEC: FFC 0707

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.3E-6	1.75	.09	.03	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05494 COATING CONFORMAL CONATHANE CE1155 POLYURETHANE GID: AKCQXX

MANF: CONAP SPEC: MIL-I-46058C

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
S	1	023.8	014.5	0.071		00.09	04.70 T	NONE
A	2	023.8	014.5	0.012		00.00	00.00	NONE
A	1	023.8	014.5	0.012			01.30	NONE
X	1	024.5	014.5	0.130		00.09	12.00 T	MOD
I	1	025.9	014.3	0.002	0.003	00.86	12.00 T	NONE
X	1	025.9	014.3	0.130		00.09	12.00 T	MOD
I	1	030.0	010.0	0.002		00.75	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

MIL-P-13949

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.33	.01		5H-70F- 1.4H-199F-

ODOR

RT	RT WEIGHT	CURE
B	00007.79	24H-140F- 3H-140F-

TOXICITY

05416 COATING CONVERSION BL OXIDE INORGANIC GID: AKXXXX

MANF: SPEC: MIL-F-495

....NO TEST DATA AVAILABLE....

00666 COATING CONVERSION CHROMATE GID: AKCQXX

MANF: APPLIED RESEARCH LAB
TELEDYNE BROWN ENG SPEC: MIL-C-5541

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.002	0.031	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	10000		200	0.032	0	20
B	MECH	1250	72	200	0.032	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00000.02	

TOXICITY

60350 COATING CORR RES KORROSION SHULTZ GID: AUXXXX

....NO TEST DATA AVAILABLE....

60148 COATING CORROSION INHIBITING COMPOUND

MANF: SPEC: MIL-C-19459

....NO TEST DATA AVAILABLE....

20223 COATING CORROSION PREVENTIVE GID: AKXXXX

MANF: AQM SPEC: MIL-C-16173G2&3

....NO TEST DATA AVAILABLE....

61549 COATING CPA5197 GREY EPOXY GID: AKBGXX

MANF: CALIFORNIA PLASTECK SPEC: FED STD 595

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	X 00002.68	1H-150F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005449 3

61546 COATING CPC3864 WHITE EPOXY GID: AKBGXX

MANF: CALIFORNIA PLASTECK SPEC: FED STD 595

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	X	00004.20	1H-150F-

TOXICITY

06366 COATING CTL/C15 EPOXY WHITE 27875 GID: ATXXXX

MANF: CHEMICAL TECHNOLOGY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.023		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.0E-6	5.76	.00	.49	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

06072 COATING CTL15/C15 CAT EPOXY BLACK GID: ATBGXX

MANF: CHEMICAL TECHNOLOGY SPEC: HMS 15-1099T1C2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		03.20	NONE
A	1	025.9	014.3	0.001			01.40	NONE
A	1	030.0	010.4	0.001			01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.81	.06	.00	1H-212F- 1H-212F- 24H-257F-

ODOR

RT	RT	WEIGHT	CURE
A	V	00007.62	24H-150F-

TOXICITY

02827 COATING D4375 VITON GID: AKXXXX

MANF: DYNATHERM CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.14	.06	.00	24H-138F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

06077 COATING D4D THERMAL CONTROL ALUMINUM/SILICONE GID: AVCKMA

MANF: GENERAL ELECTRIC SPEC: SVHS 7302

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.029	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.72	.10	.00	48H-70F- 48H-210F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60983 COATING D65/TOPCOAT 904 GID: AKXXXX

MANF: FLAMEMASTER CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.2E-6	11.98	.11	1.54	.17H-70F- 97H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

20184 COATING DAG195 CONDUCTIVE GID: AMXXXX

MANF: ACHESON COLLOIDS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005450 T

20184 COATING DAG195 CONDUCTIVE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.002	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	7.8E-7	3.30	.84		SEE MFG

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00004.54	SEE MFG

80065 COATING DAPCO 2031 FLUOROELASTOMER

MANF: D AIRCRAFT PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.072	0.003		01.90	NONE
A	1	020.9	014.7	0.101	0.020		00.80	NONE
A	1	020.9	014.7	0.155	0.003		01.20	NONE
A	1	020.9	014.7	0.053	0.020		01.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	15	-297	0.071	00	20
X	MECH	50	10	75	0.053	01	08
X	MECH	50.0	20	-150	0.063	00	20

06386 COATING DAPCOTAC 3300TH ADHESIVE GID: AKXXXX

MANF: D AIRCRAFT PRODUCTS SPEC: MB0125-087

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.008			02.40	NONE
A	1	025.9	014.3	0.003	0.003		01.40	NONE
A	1	033.0	014.3	0.003	0.003		02.40	NONE
X	1	100.0	020.2	0.003		01.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	6.2E-7	2.27	1.32		SEE TEST REPORT

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00003.41	24H-70F- 1H-150F-

64183 COATING DC 1-2577/C 176 GID: ALCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.004			03.20	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00021.80	.5H-168F-

06093 COATING DC 1107 INSUL FLUID GID: AKXXXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.013	0.010	0.1	12.00	T NONE
C	1	030.0	010.0	0.013	0.010	1.4	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	13.67	2.65	.00	1H-302F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	21.135	1H-70F- 4H-250F-

05039 COATING DC 1200 SILANE

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.001	0.003	00.00	00.00	NONE
A	1	100.0	020.2	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0005451 1

Information Handling Services, 2000

05039 COATING DC 1200 SILANE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	12.86	.02	.00	24H-70F- 24H-150F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	X	00000.11	24H-70F-

60437 COATING DC 1201 CLEAR SILICONE GID: AUCKXX

MANF: DOW CORNING SPEC: MC8006-101

....NO TEST DATA AVAILABLE....

05362 COATING DC 1203 SILANE GID: AKXXXX

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

20174 COATING DC 1204 GID: AUXXXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.30	0.003	0.003	00.08	02.25	NONE
A	1	025.9	014.3	0.001	0.003		01.10	NONE
A	1	030.0	009.0	0.001	0.003		01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.8E-6	8.78	.00	3.49	2H-70F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	B	00010.54	24H-70F- 24H-150F-

06439 COATING DC 1205 GID: AUXXXX

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

65100 COATING DC 3140/FLUOREL 7GA GID: AKXXXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.005	0.003		01.20	NONE
A	1	030.0	010.0	0.005			00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

No test data

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	B	00011.75	SEE TEST REPORT

65087 COATING DC 4-77 ENAMEL GID: AKXXXX

MANF: KOPPERS CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	.48	.00	.34	1.75H-680F-

ODOR / TOXICITY

No test data

20131 COATING DC 630 SILICONE GID: AKCKXX

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

05010 COATING DC 92-007 SILICONE GID: AKCKXX

MANF: DOW CORNING SPEC: MB0125-069

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.79	.18	.00	

ODOR / TOXICITY

No test data

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005452 3

60292 COATING DC 92-046 GID: AKXXXX
MANF: DOW CORNING SPEC: 10A00526
....NO TEST DATA AVAILABLE....

60062 COATING DC 93-104 SILICONE GID: AKCKXX
MANF: DOW CORNING SPEC: STW5-2650
....NO TEST DATA AVAILABLE....

05301 COATING DC Q3-6500 SILICONE GID: DODRXX
MANF: DOW CORNING SPEC: MA0106-325C2 MIL-I-46058

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.103	0.003		00.40	NONE
A	1	023.8	014.5	0.023	0.003		01.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		70	0.050	1	20
Z	MECH	1500	72	70	0.050	2	03

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.96	.34	.00	168H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00554.77	72H-70F- 24H-150F-

03398 COATING DC Z6020 SILANE GID: AUBGXX
MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		02.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.3E-7	17.32	.00		2H-70F-14.7psiaAMBIENT 168H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00010.03	24H-150F-

61724 COATING DC Z6031 SILANE GID: AUCKXX
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00000.21	24H-150F-

80151 COATING DC Z6040 SILANE
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.98	1.47	.00	24H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05961 COATING DC Z6070 SILANE GID: AUCKXX
MANF: DOW CORNING SPEC: MB0115-020 MB0115-021

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00000.35	

62310 COATING DCI SYSTEM 20 POLYMER GID: AKDFXX
MANF: DIVERSIFIED CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.500		00.04	04.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00098.21	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005453 5

20173 COATING DENNIS 1169 URETHANE A/B GID: AKCQXX

MANF: DENNIS CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.003			06.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.00	.01	.00	2H-199F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00008.23	

05805 COATING DEPTHANE GLOSS #1 POLIURETHANE GID: AKCQXX

MANF: DEFT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.30	NONE
B	1	025.9	014.3	0.001			08.10	NONE
A	1	030.0	009.0	0.001			02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.4E-6	8.59	.59		24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00001.03	24H-150F-

05567 COATING DER 332 RESIN/MXDA CAT GID: AKBGXX

MANF: DOW CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.013	0.003	00.00	00.00	NONE
X	1	025.9	014.3	0.013	0.003		05.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.03	.00	.50	2H-176F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.78	24H-70F-

65399 COATING DER 332/VERSAMID 125 GID: AKXXXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.010		00.10	12.00	T MOD
X	1	025.9	014.3	0.010		00.80	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00021.13	168H-70F-

20541 COATING DERUSTO 511 EPOXY WHITE GID: ATBGXX

MANF: DAP INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	20.46	

64116 COATING DIMETCOTE #6 GID: ATHAGP

MANF: AMERON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	006.2	0.003		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00018.70	24H-70F-

20691 COATING DIMETCOTE 3/AMERCOTE 383HS GID: AWBGXX

MANF: AMERON SPEC: SVHS 8513

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005454 7

20691 COATING DIMETCOTE 3/AMERCOTE 383HS (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	100.0	019.0	0.008	0.125	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	K	00842.64	

05936 COATING DK403 EPOXY DRY POWDER GID: AKBGXX

MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.021	0.003		05.10	NONE
A	1	030.0	010.0	0.010	0.003	00.10	02.70	NONE
C	2	033.0	014.3	0.021	0.003		00.40	NONE
C	1	033.0	014.3	0.021	0.003	00.37	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-7	.59	.00		.12H-400F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00021.84	.17H-400F-

05825 COATING DURACHEM 13905 EPOXY GID: ATBGXX

MANF: GRAPHTEX INC
MAAS & WALDSTEIN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.010	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	2.15	1.09	.00	.25H-55F-
					4H-140F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

20127 COATING DURACHEM 13905/DURACH 415 GID: AKBGXX

MANF: GRAPHTEX INC
MAAS & WALDSTEIN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.003	0.003		05.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.3E-6	8.92	.00		.25H-235F-
					4H-140F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00000.47	.25H-235F-
		4H-140F-

64052 COATING DURAFILM ENAMEL GID: AKXXXX

MANF: AMERICAN DURAFILM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.5E-6	.64	.01	.46	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

06160 COATING E2359A/B EPOXY GID: ATBGGS

MANF: VOLTAX CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.002	0.003	00.00	00.00	NONE
X	1	025.9	014.3	0.002	0.003		05.20	NONE
X	1	033.0	014.3	0.002	0.003	00.20	12.00	T MOD
X	2	100.0	020.3	0.002	0.003	00.32	12.00	T MOD
X	1	100.0	020.3	0.002	0.003	01.88	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005455 9

06160 COATING E2359A/B EPOXY (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	4.56	.15		168H-70F-

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE
X	00008.22	168H-70F-

60309 COATING E28-4 GID: AKXXXX

MANF: MEYER CO

....NO TEST DATA AVAILABLE....

06302 COATING E318315H FUSE EPOXY GID: AKBGXX

MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.078		00.00	00.00	NONE
A	1	030.0	009.0	0.078		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64324 COATING E393025H BLACK EPOXY GID: ATBGXX

MANF: ARMSTRONG

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00294.13	

05662 COATING E42GP22/V66KP46 EPOXY GID: AKBGXX

MANF: SHERWIN WILLIAMS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00001.30	24H-70F-
		24H-150F-

20272 COATING E755G EPOXY GID: COBGIA

MANF: U S POLYMERIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	65		250		0	20
C	MECH	65	45	250	0.080	00	20

60876 COATING E85552 RESIN WHITE EPOXY GID: ATBGXX

MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.077	0.003		00.10	NONE
A	1	030.0	010.4	0.077	0.003		00.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06098 COATING EC3901 GID: AUXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.18	.20	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

00440 COATING EC766 NITRILE/PHENOL GID: AKDJBX

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

63403 COATING ECCOCOAT EC 210 GID: AKBGXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.250		00.10	02.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005456 0

63403 COATING ECCOCOAT EC 210 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.86	.36	.00	24H-70F- 1H-167F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62130 COATING ECCOCOAT EC D35 GID: AKBGXX

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	6.0E-7	.59	.01		2H-165F- 4.5H-183F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65069 COATING EMRALON 330 GID: AKXXXX

MANF: ACHESON COLLOIDS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.001	0.003		02.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	7.0E-6	10.19	.20	1.04	.08H-70F- 1H-320F-

ODOR

RT	RT WEIGHT	CURE
	B 00003.07	.08H-70F- 1H-320F-

TOXICITY

69987 COATING ENAMEL 15251A WHITE

MANF: ELL-BEE CHEMICAL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.001	0.003		03.20	NONE
X	2	100.0	020.2	0.001	0.003	00.70	12.00	T NONE
X	1	100.0	020.2	0.001	0.003	02.80	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	6.05	.12	.16	120H-70F-

ODOR

RT	RT WEIGHT	CURE
	X 18.183	1H-75F- 2H-180F-

TOXICITY

06595 COATING ENAMEL 3C-31 POLYURETHANE WHITE GID: AKCQXX

MANF: NATIONAL PAINT AND VARNISH

....NO TEST DATA AVAILABLE....

20361 COATING ENAMEL 479 GID: AKXXXX

....NO TEST DATA AVAILABLE....

05731 COATING ENAMEL 5002 FED 595027038 GID: AKXXXX

MANF: CARDINAL PAINT CO

....NO TEST DATA AVAILABLE....

60938 COATING ENAMEL A316/A136 EXP PRIMER GID: ATBGXX

MANF: KOPPERS CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		02.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.3E-7	1.88	.03		5H-70F- 1H-250F-

ODOR

RT	RT WEIGHT	CURE
A	B 00007.49	SEE TVS CURE1

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005457 2

20377 COATING ENAMEL BLACK GID: ATXXXX
MANF: SPEC: MIL-E-480
....NO TEST DATA AVAILABLE....

61887 COATING ENAMEL C144 GID: AKXXXX
MANF: LOCKHEED

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	V	00002.54	2H-175F-

05754 COATING ENAMEL GLOSS BLACK GID: AKXXXX
....NO TEST DATA AVAILABLE....

05757 COATING ENAMEL GREY GID: ATCBXX
MANF: AEROSPACE AVIONICS SPEC: TT-E-527

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	X	00004.06	168H-70F-
			24H-150F-

05581 COATING ENAMEL HS767/EPX HS768 A1
MANF: ANDREW BROWN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.004		00.00	00.00	NONE
A	1	023.8	014.5	0.004			01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.1E-6	2.09	.00		1H-250F-
					24H-250F-0psiaVACUUM
					24H-250F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	K	00001.33	

60084 COATING ENAMEL LUSTERLESS STYRENE ALKYD GID: ATXXXX
MANF: AQM SPEC: TT-E-516
....NO TEST DATA AVAILABLE....

05790 COATING ENAMEL SEMIGLOSS GRAY GID: ATXXXX
MANF: BECKMAN INSTRUMENTS SPEC: TT-E-529

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.8E-6	6.19	.26		168H-70F-
					24H-150F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

20221 COATING ENAMEL WHITE GID: ATXXXX
MANF: TELE-MEASUREMENTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.019		00.58	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20442 COATING ENAMEL YELLOW GID: ATXXXX
MANF: AQM
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005458 4 ■

65409 COATING ENVIBAR UV1244T GID: ALXXXX

MANF: UNION CARBIDE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	5.85	.19	.37	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

60941 COATING EPICEL 3 EPOXY/CURE AGENT U GID: AKBJXX

MANF: CELANESE
SHELL CHEMICAL

SPEC: SVHS 7890 APP 2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	020.2	0.001	0.010	00.35	12.00	T NONE
X	1	100.0	020.2	0.001	0.010	00.66	12.00	T NONE
A	1	100.0	020.2	0.122	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.73	.00	.37	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	V 00016.43	.25H-70F- 2H-250F-

80174 COATING EPICO 2000 (SG054, SG116) EPOXY PAINT GID: ATXXXX

MANF: NIHON YUSHI

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.001	0.003		02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	83.20	.08	.00	.5H-176F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	B 12.277	2H-140F-

05956 COATING EPON 1001/VERSAMID 115 GID: AKBGXX

MANF: SHELL CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	9.03	.03	.14	16H-143F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

62004 COATING EPOXY 18 SERIES CONDUCTIV GID: ATBGXX

MANF: MICRO-CIRCUITS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.250			02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	A 00062.53	

62208 COATING EPOXY 3715-49-II A/B/C GID: ATBBXX

MANF: PENNWALT CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.30	NONE
A	1	100.0	014.5	0.004	0.250	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.9E-6	2.15	.28		SEE TEST REPORT

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	V 00004.88	SEE TEST REPORT

62391 COATING EPOXY 463-12-8/4593-30 GID: AKBGXX

MANF: BOSTIK FINCH
LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.048		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005459 6

62391 COATING EPOXY 463-12-8/4593-30 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.3E-6	3.37	.25	.29	4H-70F- 96H-70F- 168H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

62428 COATING EPOXY 463-12-8/A276 GID: AKBGXX

MANF: BOSTIK FINCH
LORD CORP
SEE TEST NO.84-18205

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.6E-6	3.46	.00	.34	1H-70F- 168H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

61761 COATING EPOXY A117-B GID: AKBGXX

MANF: ODETICS INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	K 00020.19	

05556 COATING EPOXY AMINE GID: AKBGAR

MANF: BOSTIK FINCH

SPEC: MB0125-074

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		02.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.9E-7	4.74	.20		168H-70F- 24H-150F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00011.22	168H-70F- 24H-150F-

60507 COATING EPOXY CF32A806 GID: AKBGXX

....NO TEST DATA AVAILABLE....

06054 COATING EPOXY E81552 ELEC INSUL GID: AKXXXX

....NO TEST DATA AVAILABLE....

20542 COATING EPOXY ENAMEL 66208 WHITE GID: ATBGXX

MANF: SEARS ROEBUCK & CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
X	X 00020.28	72H-70F- 4H-140F-

65377 COATING EPOXY ERLX1964/15274Z6SPQ GID: AKBGXX

MANF: UNION CARBIDE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	1.03	.01	.38	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05993 COATING EPOXY GRAY 36118 GID: AKBGXX

MANF: CALIFORNIA PLASTECK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.6E-6	.81	.00		1H-150F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005460 2

65140 COATING EPOXY POLAMIDE WITH POLYURETHANE OVERCOAT GID: AKBGXX
MANF: KANSAS PAINT & COLOR
SPEC: MIL-P-23377 STP-30169 MMC-STP-30170

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.040	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20261 COATING EPOXY POLYAMIDE BLACK GID: ASBGXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.80	.24	.00	2.5H-140F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62767 COATING EPOXY POLYAMIDE GRAY GID: AKBGXX
MANF:
SPEC: RCA 1986843

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.005	0.063	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	9.27	.02	.00	72H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65089 COATING EPOXY POLYAMIDE ON STAINLESS STEEL GID: AUBGXX
MANF: KANSAS PAINT & COLOR
SPEC: MMC-EPS-30027 STP-30170 STP-30169

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.050			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80139 COATING EPOXY POLYAMIDE RED 11105 GID: AKBGXX
MANF: RANDOLPH PRODUCTS
SPEC: MIL-C-22750

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64437 COATING EPOXY POLYIMIDE GID: AKBGCD
MANF:
SPEC: MC7935-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001			04.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64438 COATING EPOXY POLYIMIDE/PRIMER GID: AUBGCD
MANF:
SPEC: MC7935-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001			02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65358 COATING EPOXY PRIMER 37051 GID: AUBGXX
MANF: SIKKENS
SPEC: MIL-P-85582T1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	2.84	.45	.33	48H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61004 COATING EPOXY PRIMER A136-2CP AB GID: AUXXXX
MANF: KOPPERS CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.001	0.003		04.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005461 4

06629 COATING EPOXY SR1000 SOLDER RESIS GID: AKBGXX

MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		04.00	NONE
A	1	030.0	010.0	0.001			03.36	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.67	.71	.00	.75H-300F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00011.92	1H-300F-

06128 COATING EPOXY U122W GID: ATBGXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	030.0	010.0	0.003	0.003	00.00	08.50	NONE
B	1	030.0	010.0	0.003	0.003	0.4	08.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	9.98	1.07	.17	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	9.995	432H-70F-

05992 COATING EPOXY WHITE 37875 GID: AKBGXX

MANF: CALIFORNIA PLASTECK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.8	014.3	0.001	0.003		02.60	NONE
A	1	033.2	015.5	0.001	0.003		05.20	NONE
A	1	040.0	014.3	0.001	0.003		03.60	NONE
B	1	045.0	014.3	0.001	0.003		06.30	NONE
B	1	050.0	014.3	0.001	0.003		07.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60052 COATING EPOXY WHITE 9392/10A00528 GID: ATBGXX

MANF: RUSTOLEUM

....NO TEST DATA AVAILABLE....

62768 COATING EPOXY WHITE ON .020" AL GID: AKBGXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.015	0.020		04.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65328 COATING EPOXY WHITE TOPCOAT WITH H2 CATALYST GID: AKBIXX

MANF: SHELL CHEMICAL SPEC: SVHS 9656T2

VCM SUBS ALUM .003

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.010	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.010	0.003	01.10	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	7.76	.26	.51	336H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00021.52	336H-70F-

62183 COATING EPOXY/POLYAMIDE GID: ATBGAR

MANF: SPEC: MIL-C-22750T3C1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	9.0E-6	1.98	.28	.57	6H-150F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00007.06	6H-150F-

62456 COATING EPOXY/POLYAMIDE GID: AUBGCA

MANF: KOPPERS CO SPEC: MIL-P-23377 MIL-P-23377D

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005462 6

62456 COATING EPOXY/POLYAMIDE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.43	.02	.00	282H-70F-

ODOR

RT	RT	WEIGHT	CURE
	B	00005.22	24H-70F- 1H-250F-

TOXICITY

61439 COATING EPOXY/POLYAMIDE CONVERT GID: AUBGCD

MANF: BOSTIK FINCH SPEC: MIL-P-23377C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		01.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.2E-7	4.96	.05		60.5H-70F- 24H-150F-

ODOR

RT	RT	WEIGHT	CURE
A	X	00003.56	SEE TVS CURE 1

TOXICITY

06561 COATING EPOXY/POLYAMIDE WHITE GID: AUBGXX

MANF: FULLER O'BRIEN CORP SPEC: MB0125-006C1

....NO TEST DATA AVAILABLE....

61431 COATING EPOXY/POLYIMIDE GID: AUBGCD

MANF: DEFT SPEC: MIL-P-23377DT2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		05.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.48	.25	.41	24H-70F- 24H-150F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

61859 COATING EPOXY/SILICATE 193 GID: AKBGXX

MANF: POLY SCIENTIFIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.163		00.07	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64055 COATING EVA PATCHES GID: AQXXXX

MANF: PLASTISOL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00040.26	

TOXICITY

20510 COATING F/M-65208 PRIMER EPOXY GID: ATBGXX

MANF: DESOTO

....NO TEST DATA AVAILABLE....

20509 COATING F/M-6620F EPOXY GID: ATBGXX

MANF: DESOTO

....NO TEST DATA AVAILABLE....

62889 COATING FEP GID: AKBOXX

MANF: THERMECH ENGINEERING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	150	72	-220	0.003	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005463 8

64230 COATING FILAMENT WOUND KELVAR GID: AKJHXX
MANF: BRUNSWICK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.9E-6	2.21	.01	.72	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06004 COATING FLUORAD FC721 GID: AKEFXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	7.2E-6	7.49	.00		168H-70F-

ODOR

RT	RT WEIGHT	CURE
X	00000.37	168H-70F-

TOXICITY

60074 COATING FUNGICIDAL
MANF: SPEC: STW5-2701
....NO TEST DATA AVAILABLE....

05265 COATING FUSECOTE 879 WITH 1000 EPOXY GID: APBGXX
MANF: FUSECOTE CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.25	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data.		

TOXICITY

06344 COATING FUSECOTE REP35212-50 GID: AKBGXX
MANF: FUSECOTE CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.040	0.003		00.30	MOD
X	1	030.0	009.0	0.041	0.003		00.60	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	.56	.00		

ODOR

RT	RT WEIGHT	CURE
A	V 00031.97	

TOXICITY

62250 COATING FUSECOTE VE211-7A EPOXY GID: AKBGXX
MANF: FUSECOTE CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.004	0.003	00.04	11.90 T	NONE
X	1	025.9	014.3	0.004	0.003	01.02	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.98	.22	.00	1H-300F-

ODOR

RT	RT WEIGHT	CURE
A	B 00019.65	17H-300F-

TOXICITY

61758 COATING FUSECOTE/A34 EPOXY GID: ABBGXX
MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.008	0.003	00.00	00.00	NONE
B	1	023.8	014.5	0.008	0.003		06.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	8.4E-7	6.35	.01		72H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
A	B 00015.77	72H-70F- 24H-150F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005464 T

06460 COATING G650 FR WHITE GID: AKXXXX
MANF: OWENS ILLINOIS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.7E-6	7.93	.00	.07	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05927 COATING GAGEKOTE 5 GID: AKBGXX
MANF: W T BEAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.028	0.003	00.00	00.00	NONE
X	1	023.8	014.5	0.028	0.003	00.17	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62104 COATING GAGEKOTE 8 GID: AOXXXX
MANF: W T BEAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.001	0.003	00.00	00.00	NONE
B	1	020.9	014.7	0.001	0.003	00.65	09.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.5E-7	1.14	.00		24H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60502 COATING GLYPTAL 1201 RED
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		02.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.10	2.55	.00	4H-257F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

85452 COATING GRAY 36231 POLYAMIDE EPOXY SPEC: MIL-C-22750C1T3
MANF: TEMPO PAINT AND VARNISH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002	0.003		01.90	NONE
A	1	033.0	014.3	0.002	0.003		02.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.1E-6	1.05	.13		2H-150F-

ODOR

RT	RT WEIGHT	CURE
A	B 00013.17	2H-150F-

TOXICITY

65454 COATING GRAY PAINT SEE TEST RPT GID: ATXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	S	

TOXICITY

61779 COATING GRAY TOPCOAT/KOROPON PRIMER GID: ATAKBG
MANF: PENNWALT CORP SPEC: RC1108 4334-113

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	X 00013.84	SEE TEST REPORT

TOXICITY

62198 COATING GREY ENAMEL/PRIMER GID: ATAOXX
MANF: INMONT CORP SPEC: MIL-F-14072 TT-E-529C1A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
[illegible]				[illegible]	[illegible]	[illegible]	[illegible]	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005465 1

80181 COATING HAMMER NET 300 PAINT CAR WHITE GID: ATXXXX

MANF: OHASHI CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
B	2	024.5	014.5	0.003	0.003	00.00	00.00		NONE
B	1	024.5	014.5	0.003	0.003	0.5	08.80		NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	21.544	.75H-266F-

01276 COATING HEA LENS INORGANIC GID: AKXXXX

MANF: OPTICAL COATING LAB

....NO TEST DATA AVAILABLE....

20501 COATING HELASTIC 2010 GID: AKCQXX

MANF: WILMINGTON CHEM CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
C	2	023.8	014.5	0.006	0.003	00.00	00.00		NONE
C	1	023.8	014.5	0.006	0.003	01.00	12.00	T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.55	.15	.00	168H-46F- .5H-248F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00008.09	.5H-70F- 2.5H-200F-

20325 COATING HELASTIC 23GD102 GID: ATCQXX

MANF: WILMINGTON CHEM CO

....NO TEST DATA AVAILABLE....

61605 COATING HELASTIC 25GD102 GID: ATCQXX

MANF: WILMINGTON CHEM CO

SPEC: ST65U092 ST65U092-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	023.8	014.5	0.002			02.50		NONE
X	2	025.9	014.3	0.006	0.003	00.00	00.00		NONE
X	1	025.9	014.3	0.006	0.003	00.50	12.00	T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.01	.00		24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00019.99	24H-70F- 24H-150F-

61207 COATING HELASTIC X768 POLYURETHANE GID: ATCQXX

MANF: WILMINGTON CHEM CO

SPEC: ST65U1244-02 ST65U1244-03
ST65U1244-04 ST65U1244-05

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	025.9	014.3	0.002	0.003		05.50		NONE
X	2	025.9	014.3	0.030		00.27	12.00	T	MOD
X	1	025.9	014.3	0.030		00.14	11.80	T	MOD
I	1	030.0	009.0	0.003	0.003	00.57	12.00	T	NONE
A	1	030.0	009.0	0.002	0.003		01.00		NONE
I	1	100.0	020.2	0.002	0.003	02.50	12.00	T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.2E-6	3.10	.23	.51	16H-70F- 16H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.92	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005466 3

06618 COATING HEXAMETHYLDISILAZNE Z6079 GID: AKXXXX
MANF: DOW CORNING SPEC: MB0115-021
....NO TEST DATA AVAILABLE....

00197 COATING HFA ANTIGLAR OPTICAL GID: AKXXXX
MANF: OPTICAL COATING LAB SPEC: MIL-C-675
....NO TEST DATA AVAILABLE....

06207 COATING HI EMITTANCE/WEAR R INORGANIC GID: AKXXXX
MANF: SPEC: MA0109-316
....NO TEST DATA AVAILABLE....

05246 COATING HUMISEAL 1A20 POLYURETHANE GID: AKCQXX
MANF: COLUMBIA TECH CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.005		00.20	10.60	T MOD
X	1	023.8	014.5	0.005		01.00	11.70	T MOD
B	1	024.5	014.5	0.093		00.02	0.75	NONE
X	1	025.9	014.3	0.009	0.003	01.07	12.00	T MOD
X	1	030.0	009.0	0.018		00.77	12.00	T MOD
X	1	030.0	009.0	0.009	0.003	00.67	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.0E-7	6.98	.03		168H-70F- 24H-150F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00006.80	168H-70F- 24H-150F-

06181 COATING HUMISEAL 1A33 POLYURETHANE GID: ALCQXX
MANF: COLUMBIA TECH CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.012	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.012	0.003	00.59	12.00	T SMALL
I	1	030.0	009.0	0.006	0.003	01.01	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	9.0E-7	6.15	1.17		24H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00017.00	24H-70F-

00250 COATING HUMISEAL 1B12 ACRYLIC GID: AKAKXX
MANF: COLUMBIA TECH CORP SPEC: MB0125-057

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	030.0	010.0	0.002		00.042	00.20	NONE
A	1	030.0	010.0	0.002		00.686	05.56	NONE
C	2	030.0	010.0	0.002	0.003	00.00	00.00	NONE
C	1	030.0	010.0	0.002	0.003	0.7	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.00	.01	.00	432H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00001.60	168H-70F- 24H-150F-

05540 COATING HUMISEAL 1B31 ACRYLIC GID: AKCQXX
MANF: COLUMBIA TECH CORP
ODETICS INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.003	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005467 5

05540 COATING HUMISEAL 1B31 ACRYLIC (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
C	1	020.9	014.7	0.003	0.003	00.45	12.00	T	NONE
A	1	023.8	014.5	0.056	0.003	00.00	00.00		NONE
C	2	023.8	014.5	0.001	0.003	00.00	00.00		NONE
C	1	023.8	014.5	0.001	0.003	00.65	12.00	T	NONE
I	1	025.8	014.3	0.004		01.26	12.00	T	NONE
X	1	030.0	009.0	0.007	0.003	00.70	12.00	T	MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	11.82	.08	.00	.5H-176F-

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
A	X	00001.23	24H-70F-

69822 COATING HUMISEAL 1B73 GID: ALXXXX

MANF: COLUMBIA TECH CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
I	1	030.0	010.0	0.001	0.001	0.80	12.00	T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
A	X	4.98	

05919 COATING HUMISEAL 2A64A/B POLYURETHANE GID: ATCQXX

MANF: COLUMBIA TECH CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	023.8	014.5	0.005	0.003		01.70		NONE
X	1	030.0	009.0	0.011	0.003	00.53	12.00	T	MOD
C	2	030.0	010.0	0.014	0.010	00.09	12.00	T	NONE
C	1	030.0	010.0	0.014	0.010	1.6	12.00	T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.47	.03	.00	3H-171F- 120H-46F-

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
A	B	00001.58	3H-170F- 120H-70F-

05360 COATING HUMISEAL 2A72 POLYURETHANE GID: BDCQXX

MANF: COLUMBIA TECH CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	9.38	.02	.00	2H-151F-0psiaVACUUM

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
A	B	00230.06	24H-150F-

20116 COATING HYDROPHILIC ZN O/SILICONE GID: AKDPXX

....NO TEST DATA AVAILABLE....

00552 COATING HYPALON 150W-8 GID: ATXXXX

MANF: GACO WESTERN INC SPEC: MB0125-011

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.8E-6	1.46	.08		24H-138F-

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	X	00001.84	24H-150F-

62769 COATING HYPALON HFR2200 WHITE GID: AKDCXX

MANF: GACO WESTERN INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
I	1	020.9	014.7	0.250			08.00		NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005468 7

60229 COATING HYPALON/GACOFLEX H2200 WHITE
MANF: GACO WESTERN INC SPEC: STW5-2983
....NO TEST DATA AVAILABLE....

60225 COATING HYPALON/GACOFLEX HFR2200
MANF: GACO WESTERN INC SPEC: STW5-2994 USB-MS-5002
....NO TEST DATA AVAILABLE....

20352 COATING IMPREGNANT GLOVE POLYURETHANE GID: AKCQXX
MANF: ILC DOVER SPEC: ST65U092-03 ST65U092-04

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.035		00.33	02.00	T MOD
X	1	025.9	014.3	0.035		00.18	02.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.6E-7	1.49	.06		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00020.00	

20546 COATING INDOTHANE 441-1C-41 WHITE GID: ATBGXX
MANF: DAP INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE
X	00020.06	

65251 COATING INK 002-0001-01 STAMP GID: APXXXX
MANF: APPLETON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.3E-6	1.37	.45	.07	1H-300F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

65184 COATING INK ON PAPER FROM HP2225A GID: APXXXX
MANF: HEWLETT-PACKARD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00015.18	

63511 COATING INK/ADHESIVE ON LEXAN GID: APXXXX
MANF: 3M CO
COLONIAL PRINTING
GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.011		00.51	10.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00007.50	

62770 COATING INORGANIC WHITE GID: ATXXXX
MANF: NASA/GSFC SPEC: MMC/STM K792

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.004	0.040	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

00926 COATING INSULUBE 448 URETHANE GID: AKCQXX
MANF: INTERNATIONAL ELECTRONIC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005469 9

65062 COATING IRIDITE 14-2/CHROMATE GID: AKXXXX

MANF: ALLIED PRODUCTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	0.403	

TOXICITY

05633 COATING IRIDITE 7 INORGANIC GID: AKXXXX

MANF: WITCO

....NO TEST DATA AVAILABLE....

05727 COATING ISONEL 31 POLYESTER GID: AKXXXX

MANF: SCHENECTADY VARNISH SPEC: MIL-V-1137GCB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		02.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.8E-7	2.61	.57		2H-300F-

ODOR

RT	RT	WEIGHT	CURE
	A	V 00005.16	2H-300F-
			2H-300F-

TOXICITY

63473 COATING KODAK REFLECTIVE WHITE GID: AKXXXX

MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	.05	.02	.02	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

61392 COATING KONFORM SILICONE GID: ALCKXX

MANF: CHEMTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		00.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-6	4.32	.47	.29	

ODOR

RT	RT	WEIGHT	CURE
	X	00003.83	1H-70F-
			24H-70F-

TOXICITY

61226 COATING KOROPON SUPER HI TEMP GID: AUBMXX

MANF: DESOTO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.64	.17	.00	SEE TEST REPORT

ODOR

RT	RT	WEIGHT	CURE
	B	00005.80	168H-70F-
			24H-150F-

TOXICITY

05893 COATING KP420/6383 GID: AUXXXX

MANF: PRATT & LAMBERT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20477 COATING KRYLON 1301 CLEAR GID: AKXXXX

MANF: BORDEN SPEC: MB0125-086

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001			04.60	NONE
C	2	025.9	014.3	0.001	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.001	0.003	00.85	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.0E-6	9.80	.22	.08	24H-70F-

ODOR

RT	RT	WEIGHT	CURE
	A	X 00002.24	SEE MFG

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005470 5

20477 COATING KRYLON 1301 CLEAR (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					24H-150F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE

60708 COATING KRYLON 150 CRYSTAL WHITE GID: AKXXXX

MANF: BORDEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.002	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.002	0.003	01.69	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	6.0E-6	1.54	.11		24H-70F-
					24H-150F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00006.86	24H-70F-
		24H-150F-

06305 COATING KRYLON 1501 GLOSSY WHITE GID: AKAAXX

MANF: BORDEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		03.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60754 COATING KRYLON 1602 GID: ATAKXX

MANF: BORDEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.001			00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.93	.46	.00	168H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	X 2.935	360H-70F-

60313 COATING KRYLON LACQUER BLACK GID: AKXXXX

MANF: BORDEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.001	0.250	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	V 4.223	

60259 COATING KRYLON RED-ORANGE GID: ATXXXX

MANF: BORDEN

....NO TEST DATA AVAILABLE....

61603 COATING L496A-66/37038 CAM LACQURE GID: ASXXXX

MANF: ANDREW BROWN SPEC: TT-L-20A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00003.50	168H-70F-
		24H-150F-

64439 COATING LAC-O-RITE GID: ATXXXX

MANF: SINCLAIR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005471 7

61886 COATING LAC37-722A TY2/TT-P1757 GID: AKXXXX

MANF: LOCKHEED

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
B	00011.57	SEE MANUFACTURER

20194 COATING LACQUER 604-37038 GID: ASXXXX

MANF: SPEC: MIL-L-6805

....NO TEST DATA AVAILABLE....

60122 COATING LACQUER ACRYLIC

MANF: SPEC: TT-L-50T2

....NO TEST DATA AVAILABLE....

65121 COATING LACQUER BLACK 32178-66 GID: ASXXXX

MANF: TRAIL CHEMICAL CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	5.35	.66	.34	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

60261 COATING LACQUER CELLULOSE NITRATE GID: ASXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	0.001	0.003	2.2	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.39	.02	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
X	14.066	1H-122F-

06487 COATING LACQUER NO.2 OSC877 GID: ASXXXX

MANF: WESFIELD CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.50	.03	.16	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

20063 COATING LACQUER PAINT QUICK DRY GID: AKXXXX

MANF: AQM SPEC: MIL-I-17384TG

....NO TEST DATA AVAILABLE....

20218 COATING LACQUER STICK BLACK GID: ATXXXX

MANF: LAKE CHEMICAL CO SPEC: TT-F-325A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
X	00009.66	

02691 COATING LADICOTE COMPOSITE GID: AKXXXX

MANF: SPEC: STO125LB0001

....NO TEST DATA AVAILABLE....

00042 COATING LAMINAR X500 POLYURETHANE GID: AKCQXX

MANF: MAGNA CTNG & CHEM SPEC: MBO125-002

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	20.44	.10	.00	72H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

02468 COATING LAMINATE FLEXIBLE/ALUMINUM/M-FILM

MANF: SPEC: MBO125-043

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005472 9

60662 COATING LATEX 1500 FLAMEREST GID: AKACXX

MANF: AVCO SYSTEMS TEXTRON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	9.0E-7	9.06	3.04		4H-70F-

ODOR

RT	RT	WEIGHT	CURE
	X	00026.37	4H-70F-

TOXICITY

62065 COATING LATEX 3715-16-1 A/B EPOXY GID: ATBGXX

MANF: PENNWALT CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.1E-6	5.57	1.31		168H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	X	00004.70	168H-70F-

TOXICITY

62064 COATING LATEX 3715-24-1 A/B TC GID: ATEFBG

MANF: PENNWALT CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.1E-6	1.13	.10		168H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	X	00010.52	168H-70F-

TOXICITY

62192 COATING LATEX 3715-25-2 A/B GID: ATEFAK

MANF: PENNWALT CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.1E-6	1.34	.28		168H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	V	00006.26	168H-70F-

TOXICITY

61216 COATING LATEX 3715-26-1 A/B GID: ATEFBG

MANF: PENNWALT CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003		01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.1E-6	1.91	.21		168H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	X	00007.90	168H-70F-

TOXICITY

60694 COATING LATEX 4367-3 UNPIGMENTED GID: ATACXX

MANF: PENNWALT CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.4E-6	.89	.05		

ODOR

RT	RT	WEIGHT	CURE
A	X	00004.76	24H-70F-

TOXICITY

60883 COATING LATEX 4699-121B GID: ATACXX

MANF: PENNWALT CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.2E-7	.84	.03		24H-70F-
					72H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60448 COATING LATEX 4699-126 GID: ATBPXX

MANF: PENNWALT CORP

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005473 0

60448 COATING LATEX 4699-126 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	X	00009.18	24H-70F-

06063 COATING LATEX FRL3 FLAME RETARDANT GID: AKACXX

MANF: SPEC: MB0125-078

....NO TEST DATA AVAILABLE....

06430 COATING LATEX VINYL WT102 GID: CFXXXX

MANF: FIRE TECT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.086			00.10	NONE
A	1	025.9	014.3	1.086			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05347 COATING LC4 CR203 (INORGANIC) GID: AKXXXX

....NO TEST DATA AVAILABLE....

60413 COATING M COAT GID: AKXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.14	.08	1.68	168H-46F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

05613 COATING MACUMASK 9446 EPOXY GID: ABBMXX

MANF: MAC DERMID INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		02.10	NONE
A	1	023.8	014.5	0.004	0.003		02.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	V	00007.64	1H-250F-

06278 COATING MASKANT 204-2 EPOXY BASE GID: AKBGXX

....NO TEST DATA AVAILABLE....

61192 COATING MC7755-03 K1041 POLYURETHANE GID: AKCQFK

MANF: MIDWEST PAINT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	X	00004.02	12H-200F-
			168H-70F-

61191 COATING MC7755-03 TOPCOAT DC3140 GID: AKCQMA

MANF: MIDWEST PAINT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	V	00012.75	12H-70F-

69850 COATING MEPCO FLEX

MANF: CENTRAL LAB INC
MEPCO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-6	.61	.02	.31	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005474 2 ■

69823 COATING MEPCO FR14 CONFORMAL GID: ALXXXX

MANF: CENTRAL LAB INC
MEPCO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-6	.55	.02	.24	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06058 COATING METAL BLUEING (INORGANIC)

....NO TEST DATA AVAILABLE....

61579 COATING METALOX/31G6/11X2/50C3 GID: ATCQXX

MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.005	0.063	00.00	00.00	NONE
A	1	030.0	009.0	0.005	0.063		00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20424 COATING MO-201 EPOXY GID: ATBGXX

....NO TEST DATA AVAILABLE....

05518 COATING MOIST BARRIER SIM-HRSI GID: AKDCXX

MANF: ROCKWELL

SPEC: MB0125-044T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.004			02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	9.3E-6	4.10	4.11		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05517 COATING MOIST BARRIER SIM-LRSI GID: AKDCXX

MANF: ROCKWELL

SPEC: MB0125-044

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	9.3E-6	4.17	.09		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

69816 COATING MOLYKOTE 3400A CORROSION PROTECTIVE GID: AKXXXX

MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	6.0E-6	.15	.01	.16	1H-400F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05951 COATING MXP130 GID: AKXXXX

....NO TEST DATA AVAILABLE....

62771 COATING MXSA GID: AKXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.250	0.125	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62772 COATING MXSA/TURCO T6109/AL(OH)3 GID: AKXXXX

MANF: TURCO PROD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.187	0.125		01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005475 4

62772 COATING MXSA/TURCO T6109/AL(OH)3 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.156	0.125		01.00	NONE
A	1	020.9	014.7	0.187	0.125		06.00	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

62773 COATING MXSA/TURCO T6109/MG(OH)2 GID: AKXXXX

MANF: TURCO PROD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.187			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62774 COATING MXSA/TURCO T6109/OXALIC GID: AKXXXX

MANF: TURCO PROD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.187			10.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62775 COATING MXSA/TURCOT6109/HYP H2200 GID: AKXXXX

MANF: TURCO PROD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.375			08.00	NONE
I	1	020.9	014.7	0.375		00.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20565 COATING N136 EPOXY ENAMEL GID: ATBGXX

....NO TEST DATA AVAILABLE....

06073 COATING WA7509-V73/WA7486-V66 PLU GID: AKBGXX

MANF: SHERWIN WILLIAMS SPEC: SVHS 7890

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.041	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.041	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00206.83	

20250 COATING NAZDAR ER111 GID: ARBGXX

MANF: NAZ DAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.001			00.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.4E-6	9.96	.50	.52	

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE
X	00006.20	

20386 COATING NEDOX SF2 TEFLON GID: AKCNXX

MANF: GENERAL MAGNAPLATE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002	0.010		01.40	NONE
X	1	100.0	020.2	0.002	0.010	00.37	11.80	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-7	.04	.00		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00006.49	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005476 6

00968 COATING NEOPRENE LN2500A GID: AZDBXX

MANF: GOLDEN STATE/LATEX SPEC: MIL-R-3065SC515

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.7E-6	2.43	.65		

ODOR

RT	RT	WEIGHT	CURE
A	A	00078.73	

TOXICITY

06540 COATING NEXTEL 3101-C10 GID: ATCBXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002			05.20	NONE
A	1	030.0	009.0	0.002			05.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	7.0E-6	2.36	.11	.50	2H-70F-ONE BRUSH COAT OF PRIMER WAS APPLIED. 24H-70F-ONE BRUSH COAT OF BLENDED PAINT WAS APPLIED OVER CURED PRIMER COAT. 24H-150F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00015.82	SEE MFG

TOXICITY

64106 COATING NEXTEL 900 WHITE GID: ARXXXX

MANF: COOK PAINT & VARNISH SPEC: SV3148 THINNER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.008		00.20	02.80	SMALL
A	1	030.0	010.0	0.005		00.18	02.90	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00006.49	

TOXICITY

20172 COATING NEXTEL 901P 1 GID: AUXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	B	00003.72	24H-70F- 24H-150F-

TOXICITY

61551 COATING NYEBAR TYPE CT GID: AKEFXX

MANF: WILLIAM F NYE INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.001		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	X	00000.04	

TOXICITY

05804 COATING NYTUFF TEFLON ANODIZED GID: AKCNXX

MANF: NIMET IND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010	0.003	00.00	00.00	NONE
A	1	030.0	009.0	0.010	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	245	72	120	0.052	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005477 8

05804 COATING NYTUFF TEFLON ANODIZED (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	033.0	014.3	0.010	0.003	00.00	00.00	NONE
A	1	100.0	019.0	0.010	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.68	.00		

ODOR

RT	RT	WEIGHT	CURE
	A	00023.97	

TOXICITY

61790 COATING ONCOR M50 LATEX GID: ATAKXX

MANF: PENNWALT CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.3E-6	2.05	.03		24H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

61706 COATING ONCOR M50/ZNCHR 4334-109 GID: ATAAAH

MANF: PENNWALT CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	1.31	.00		24H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00009.22	24H-70F-

TOXICITY

20722 COATING OPTICAL ZN SULFIDE-INORGANIC

....NO TEST DATA AVAILABLE....

20721 COATING OPTICAL MAG FLUORIDE-INORGANIC

....NO TEST DATA AVAILABLE....

20723 COATING OPTICAL SI MONOXIDE-INORGANIC

....NO TEST DATA AVAILABLE....

62372 COATING P527D/C527D/PRIMER GID: AUXXXX

MANF: KOPPERS CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.16	.04	.00	.25H-70F-
					1H-171F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

80297 COATING PAINT YELLOW 33798 URETHANE/PRIMER EPOXY AMIDE GID: ATXXXX

MANF: DESOTO
DESOTO/ADVANCED PROD

SPEC: MIL-C-83286:PAINT MIL-P-23377:PRIMER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.005	0.005	0.26	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60838 COATING PARYLENE D GID: AKBGIA

MANF: UNION CARBIDE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.2E-7	.12	.02		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05657 COATING PC 29/29M POLYURETHANE GID: COCKXX

MANF: HYSOL/DEXTER

SPEC: MC409-0126 MIL-I-46058

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		00.48	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005478 T

05657 COATING PC 29/29M POLYURETHANE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	023.8	014.5	0.010			02.30		NONE
X	1	024.5	014.5	0.001		00.60	12.00	T	MOD
X	2	025.9	014.3	0.004	0.003	00.00	00.00		NONE
X	1	025.9	014.3	0.004	0.003	00.50	12.00	T	MOD
I	1	030.0	010.0	0.001	0.003	00.70	12.00	T	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.42	.10	.00	2H-140F-

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	9.81	.35H-70F- 2H-212F-

05249 COATING PC12-007 EPOXY GID: ATBGXX

MANF: HYSOL/DEXTER

SPEC: MIL-I-46058ER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.002		00.25	05.20	SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.6E-7	7.67	.11		

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE
X	00017.31	168H-70F-

64973 COATING PC17/17M POLYURETHANE GID: COCKXX

MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	020.9	014.7	0.130			00.40		SMALL
I	1	024.5	014.5	0.130		00.09	12.00	T	SMALL
I	1	025.9	014.3	0.130		00.09	12.00	T	SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	13.85	.08	.00	168H-70F-

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00006.16	3H-140F- 24H-176F-

06382 COATING PC18/18M POLYURETHANE GID: COCKXX

MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	020.9	014.7	0.130			00.70		SMALL
I	1	024.5	014.5	0.130		00.01	12.00	T	SMALL
X	1	025.9	014.3	0.130		00.09	12.00	T	MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	1.04	.05	.00	16H-122F- 24H-176F-

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00004.22	24H-140F- 3H-140F-

06405 COATING PC210 FIRE RETARDANT GID: AKXXXX

MANF: FIRE TECT

....NO TEST DATA AVAILABLE....

20529 COATING PEDIGREE 923 EPOXY VARNISH GID: AKCQXX

MANF: P D GEORGE CO

SPEC: SVHS 7873

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.052		00.00	00.00	NONE
A	1	033.0	014.3	0.052		00.00	00.00	NONE
A	1	100.0	019.0	0.052		00.00	00.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005479 1

20529 COATING PEDIGREE 923 EPOXY VARNISH (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.02	.00		

ODOR

RT	RT	WEIGHT	CURE
A	K	00529.77	

TOXICITY

60485 COATING PENNWALT 4699-121-A GID: ATXXXX

MANF: PENNWALT CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.1E-7	.70	.04		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60484 COATING PENNWALT 4699-122-A GID: ATACXX

MANF: PENNWALT CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	100.0	060.0	0.255			00.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.1E-7	.85	.04		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

20440 COATING PHENOLIC BASE GID: ATXXXX

MANF: R O HULL

....NO TEST DATA AVAILABLE....

06399 COATING PHENOLIC P-5 PRIMER GID: AUBXXX

MANF: DAYTON PRODUCTS

....NO TEST DATA AVAILABLE....

60072 COATING PHENOLIC SC 1008 GID: AUBXXX

MANF: MONSANTO

....NO TEST DATA AVAILABLE....

05559 COATING PHOSPHATE (INORGANIC) GID: AKXXXX

MANF: SPEC: AMS 2481 MIL-P-16232TM

....NO TEST DATA AVAILABLE....

65426 COATING PIPE SEALANT ON FIBERGLASS GID: AKXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.100		00.10	11.70	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-314	0.100	01	12
X	MECH	50	20	-297	0.100	01	01
B	MECH	50	72	70	0.100	00	20

06206 COATING PLASMA CHROMIC OXIDE INORGANIC GID: AKXXXX

MANF: SPEC: LA109-041

....NO TEST DATA AVAILABLE....

06351 COATING PLASTIDIP 9560T12 GID: AKXXXX

MANF: MCMASTER CARR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.077		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65051 COATING PLV2000 HS GID: AKDEXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010	0.003		01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005480 8

65051 COATING PLV2000 HS (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00014.72	

TOXICITY

05778 COATING PLYTILE R294-151B EPOXY GID: ATBGCD

MANF: M A BRUDER & SONS

SPEC: HK6658 HK6690 MIL-C-22751

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.6E-6	10.13	.33		

ODOR

RT	RT	WEIGHT	CURE
	X	00005.60	1H-70F- 192H-70F-

TOXICITY

05004 COATING PM47 PRIMER GID: ABBGXX

MANF: AMERICAN CYANAMID

SPEC: MB0120-031

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	X	00003.54	24H-150F-

TOXICITY

64330 COATING POLANE ENAMEL GID: AKXXXX

MANF: SHERWIN WILLIAMS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	1.35	.04	.38	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

65113 COATING POLANE F63 VI GID: AKXXXX

MANF: SHERWIN WILLIAMS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.2E-6	17.17	.09	.27	24H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

20270 COATING POLANE F63CB2/V66V29 GID: AKCQXX

MANF: SHERWIN WILLIAMS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.400		00.16	10.80	NONE
A	1	020.9	014.7	0.400		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	27.48	.04	.00	24H-46F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

63762 COATING POLANE TOPCOAT/KEVLAR GID: COHSBG

MANF: ARDE
BRUNSWICK
SHERWIN WILLIAMS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.130		00.07	02.60	NONE
C	2	020.9	014.7	0.150		00.00	00.00	NONE
C	1	020.9	014.7	0.150		00.10	07.40	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.2E-6	4.65	.08	1.18	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005481 T

05135 COATING POLYAMIDE EPOXY GID: AUBGAR
MANF: DEFT
SPEC: MIL-P-23377 MIL-P-23377D

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.9E-6	2.41	.51	.43	720H-70F-

ODOR

RT	RT	WEIGHT	CURE
	B	00007.91	24H-70F- 1H-250F-

64883 COATING POLYAMIDE EPOXY GID: AUBGAR
MANF: DESOTO
SPEC: MIL-P-23377C

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001			03.50	NONE
A	1	033.0	014.3	0.001			03.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.1E-6	.92	.10		

ODOR

RT	RT	WEIGHT	CURE
A	B	00011.97	168H-70F- 24H-150F-

64884 COATING POLYAMIDE EPOXY GID: AUBGAR
MANF: TEMPO PAINT AND VARNISH
SPEC: MIL-P-23377C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002	0.003		02.70	NONE
A	1	033.0	014.3	0.002	0.003		04.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.79	.03	.00	24H-149F-

ODOR

RT	RT	WEIGHT	CURE
A	V	00009.87	

65175 COATING POLYAMIDE EPOXY PRIMER YELLOW GID: AUXXXX
MANF: SHERWIN WILLIAMS
SPEC: MIL-P-23377

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	X	00006.23	

20070 COATING POLYAMIDE RED 11136 EPOXY GID: ATXXXX
MANF: AQM
SPEC: MIL-C-22750

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	X	00003.01	24H-70F- 24H-150F-

65098 COATING POLYAMIDE WITH CHEMGLAZE Z306 GID: AKCDXX
MANF: LORD CORP
SPEC: MIL-P-23377 MMC-STP-30170
STP-30151

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.67	.08	.00	2H-70F- 336H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

80239 COATING POLYFLON SPRAY WAX GID: APXXXX
MANF: DAIKIN KOGYO CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	6.522	

20799 COATING POLYIMIDE BLACK 37038 EPOXY GID: ATCDXX
MANF: AQM
SPEC: MIL-C-22750

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005482 1

20799 COATING POLYIMIDE BLACK 37038 EPOXY (cont)

MANF: DEFT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001			01.70	NONE
A	1	025.9	014.3	2.400		00.24	02.40	NONE
A	1	030.0	010.0	0.001		00.30	02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-6	.88	.00	.82	24H-70F- 48H-350F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00022.27	168H-70F-

64885 COATING POLYIMIDE EPOXY YELLOW TC GID: AUBGAR

MANF: SHERWIN WILLIAMS

SPEC: MIL-P-23377 TC MIL-C-83286

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00824.20	.18H-70F-

80206 COATING POLYTHANE CP500 SERIES/VINYL PHENOLIC VPP-702 PRIMER GID: AKXXXX

MANF: PRESERVO PAINT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	088.2	0.009	0.125		00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20283 COATING POLYURETHANE (ESTER) GID: AKCQXX

MANF: SHERWIN WILLIAMS

SPEC: SVHS 7873T1

....NO TEST DATA AVAILABLE....

60293 COATING POLYURETHANE 100 EPOXY WHITE GID: AKBGXX

MANF: ADVANCED PROCESS

SPEC: 16A10229

....NO TEST DATA AVAILABLE....

60294 COATING POLYURETHANE 710 EPOXY BLACK GID: ATCQXX

MANF: ADVANCED PROCESS

SPEC: 16A10228

....NO TEST DATA AVAILABLE....

64922 COATING POLYURETHANE BLACK GID: AKCQXX

MANF: DEFT

SPEC: MIL-C-83286

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.7E-6	.85	.04		168H-70F- 24H-257F-0psia20E-4

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

64926 COATING POLYURETHANE BLACK GID: AKCQXX

MANF: CARDINAL PAINT CO

SPEC: FED STD 5954

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.007	0.003	00.80	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.41	.01	.00	312H-46F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00015.65	25H-70F-

80281 COATING POLYURETHANE CLEAR GLOSS VARNISH ON INSTA-FOAM A67 V1

MANF: SHERWIN WILLIAMS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	3.500	0.188		11.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005483 3

64079 COATING POLYURETHANE CONFORMAL U2863 GID: ALXXXX

MANF: STERLING DIV OF REICHHOLD CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.4E-6	3.38	.00	.64	24H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20143 COATING POLYURETHANE ER41 CLE GID: ATCQXX

MANF: JOHN C DOLPH CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	X 00004.52	24H-70F- 24H-150F-

TOXICITY

60424 COATING POLYURETHANE LACK181/3 GID: ATCQXX

MANF: AEG-KASSEL

....NO TEST DATA AVAILABLE....

64925 COATING POLYURETHANE LT GRAY 36622 GID: AKDUXX

MANF: DEFT SPEC: MIL-C-83286

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002	0.003	00.59	06.50	NONE
A	1	025.9	014.3	0.003	0.020		01.10	NONE
A	1	033.0	014.3	0.003			01.70	NONE
A	1	100.0	020.2	0.003			05.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.2E-7	1.59	.00		24H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
A	X 00012.05	24H-70F- 24H-150F-

TOXICITY

05953 COATING POLYURETHANE ORANGE INTL 12197 GID: ATCRXX

MANF: ADVANCED COATINGS SPEC: MIL-C-83286

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	B 00019.89	.25H-70F- 2H-250F- 168H-70F-

TOXICITY

20745 COATING POLYURETHANE PLENUM .0575THK

....NO TEST DATA AVAILABLE....

20724 COATING POLYURETHANE PLENUM FILM GID: ATCQXX

MANF: ILC DOVER SPEC: ST65U092-06 ST65U092-07

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.030		00.22	06.10 T	MOD
X	1	025.9	014.3	0.030		00.16	06.60 T	MOD
X	2	025.9	014.3	0.025		00.25	06.10 T	NONE
X	1	025.9	014.3	0.025		00.36	06.40 T	MOD
X	1	030.0	009.0	0.030		00.31	06.10 T	MOD
X	1	030.0	009.0	0.025		00.29	06.40 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.37	.09	.00	

ODOR

RT	RT WEIGHT	CURE
A	A 00019.96	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005484 5

62776 COATING POLYURETHANE PR1060D GID: AKCQXX
MANF: PROD RESEARCH & CHEM
SPEC: DPM 3883 STM-0532-01 STM 0532-01 STM0532-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.004	0.003		01.02	NONE
X	1	025.9	014.5	0.019		00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00033.50	16H-140F-

61723 COATING POLYURETHANE PR1120 GID: AKCQXX
MANF: PROD RESEARCH & CHEM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00003.46	24H-150F-

06105 COATING POLYURETHANE PR1506 GID: AUCQXX
MANF: PROD RESEARCH & CHEM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.97	.05	.00	24H-77F- 16H-179F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05846 COATING POLYURETHANE PR1535 GID: ATCQXX
MANF: PROD RESEARCH & CHEM
SPEC: P/N 9005960-1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.2	0.036	0.066		00.25	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.68	.11	.00	7H-77F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

61141 COATING POLYURETHANE PR1546 GID: ATCQXX
MANF: PROD RESEARCH & CHEM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.53	.05	.00	48H-180F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

06106 COATING POLYURETHANE PR1564 GID: AUCQXX
MANF: PROD RESEARCH & CHEM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.74	.02	.00	24H-185F- 72H-212F-0psiaVACUUM

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

62291 COATING POLYURETHANE PR1568 CONFORMAL GID: ALCQXX
MANF: PROD RESEARCH & CHEM
SPEC: MIL-I-46058TYUR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.004		02.00	12.00	T NONE
A	1	024.5	014.5	0.002			05.00	NONE
A	1	025.9	014.3	0.002			06.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.25	.02	.00	1H-70F- 24H-167F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00028.10	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005485 7

62777 COATING POLYURETHANE PR1568M GID: AKCQXX

MANF: PROD RESEARCH & CHEM

SPEC: DPM 4875-1

STM 0532-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.003	0.003	02.00	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.29	.05	.00	1H-70F- 3H-180F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05949 COATING POLYURETHANE PR1654 GID: AKDUXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.011	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.011	0.003	00.62	12.00	T NONE
X	1	030.0	010.0	0.011		00.60	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.15	.04		24H-70F- 24H-150F-

ODOR

RT	RT	WEIGHT	CURE
A	V	00017.67	24H-70F- 24H-150F-

TOXICITY

06104 COATING POLYURETHANE PR420 GID: AUCQXX

MANF: PROD RESEARCH & CHEM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.67	.01	.00	24H-257F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05766 COATING POLYURETHANE RED 21105 GID: ATCQXX

....NO TEST DATA AVAILABLE....

06528 COATING POLYURETHANE SATURN YELLOW 21517 GID: ATXXXX

....NO TEST DATA AVAILABLE....

69974 COATING POLYURETHANE TOPCOAT #1 GID: AKCQXX

MANF: DESOTO
SOUTHERN MILLS

SPEC: MIL-C-83286T1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	X	21.57	

TOXICITY

69946 COATING POLYURETHANE TOPCOAT #2 GID: AKCQXX

MANF: DESOTO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	X	21.01	

TOXICITY

69945 COATING POLYURETHANE TOPCOAT #3 GID: AKCQXX

MANF: DESOTO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	X	18.08	

TOXICITY

64888 COATING POLYURETHANE WHITE GID: ATCQXX

MANF: DEFT

SPEC: MIL-C-83286

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.024			00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005486 9

06610 COATING POLYURETHANE YELLOW 23785 GID: ATCQXX

MANF: DEFT SPEC: MIL-C-83286

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.002	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.002	0.003	00.67	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	5.8E-6	2.02	.00	1.04	168H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00020.88	168H-70F- 24H-150F-

64924 COATING POLYURETHANE YELLOW 33538 GID: ATCQXX

MANF: DEFT SPEC: MIL-C-83286

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.4E-6	3.04	.09		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

62062 COATING POLYURETHANE YELLOW/SUPER KOROPON GID: AKCQBG

MANF: DEFT SPEC: MIL-C-83286
DESOTO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.020	00.00	00.00	NONE
A	1	023.8	014.5	0.005	0.020	00.00	00.00	NONE
A	1	023.8	014.5	0.010	0.030	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.4E-6	1.23	.02		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

65526 COATING PR484TC/PR475S/PR19 PR GID: ATXXXX

MANF: PROD RESEARCH & CHEM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	2.39	.13	.46	2H-70F- 8H-70F- 168H-70F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

62780 COATING PR855 SEMCO GID: AKXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.750		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64991 COATING PRC NO 1 SEE TEST REPORT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
X	HYZE
X	MMH
X	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64992 COATING PRC NO 2 SEE TEST REPORT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE
X	MMH
X	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005487 0

65010 COATING PRC NO 21 SEE TEST RPT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X		No test data						
									X	HYZE							
									X	N204							

64993 COATING PRC NO 3 SEE TEST REPORT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

64994 COATING PRC NO 4 SEE TEST REPORT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

64995 COATING PRC NO 5 SEE TEST REPORT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									A	HYZE	No test data						
									X	MMH							
									X	N204							

64996 COATING PRC NO 6 SEE TEST REPORT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

64997 COATING PRC NO 7 SEE TEST REPORT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

64998 COATING PRC NO 8 SEE TEST RPT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									A	HYZE	No test data						
									X	MMH							
									X	N204							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005488 2

64999 COATING PRC NO 9 SEE TEST RPT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

65011 COATING PRC22 SEE TEST REPORT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

65012 COATING PRC23 SEE TEST REPORT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

65013 COATING PRC24 SEE TEST REPORT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

65014 COATING PRC25 SEE TEST REPORT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

65015 COATING PRC26 SEE TEST REPORT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

65016 COATING PRC27 SEE TEST REPORT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY								FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data									X	HYZE	No test data						
									X	MMH							
									X	N204							

MSFC-HDBK-527 REV F 9999942 0005489 4

Information Handling Services, 2000

65017 COATING PRC28 SEE TEST REPORT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
X	HYZE
X	MMH
X	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65018 COATING PRC29 SEE TEST REPORT GID: ATXXXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
X	HYZE
X	MMH
X	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60213 COATING PRECUSSION GID: AKXXXX

MANF:

SPEC: MIL-P-20444

....NO TEST DATA AVAILABLE....

05764 COATING PREPARAKOAT 3055S GID: AUCBXX

MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.43	.37	.00	24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00003.60	24H-150F-

61601 COATING PRIMER GID: AKXXXX

MANF: KOPPERS CO

SPEC: MIL-P-15328C

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00001.39	168H-70F-
		24H-150F-

85394 COATING PRIMER CONVERSION CHROMATE

MANF: APPLIED RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.002	0.003		10.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00006.66	4H-70F-

61577 COATING PRIMER LOCTITE GR-T GID: AUBGXX

MANF: LOCTITE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	100	72	250	0.001	0	20

65253 COATING PRIMER POLYCLUTCH GID: AUXXXX

MANF: PPG INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	100.0	019.0	0.001	Q.003		00.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	9.67	.96	.86	336H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00001.75	24H-158F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005490 0

65253 COATING PRIMER POLYCLUTCH (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR

RT	RT WEIGHT	CURE

TOXICITY

2H-750F-

06518 COATING PRIMER SAFETY WALK GID: AUXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.004	0.003		35.00	NONE
B	1	025.9	014.7	0.004	0.003		10.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20725 COATING PRIMER SS4120 GID: AUXXXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	030.0	009.0	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	24.98	14.60	.00	24H-70F-

ODOR

RT	RT WEIGHT	CURE
A	B 00000.63	1H-70F-

TOXICITY

62815 COATING PRIMER TFE TEST DISCS GID: AUCNXX

MANF: AMETEK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.001	0	20

06300 COATING PRIMER VINYL BUTYRAL GID: AUXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	30.31	5.07	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

01843 COATING PRIMER WASH GID: AUXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.06	.33	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65105 COATING PRIMER/CHEMGLAZE A276 GID: AUXXXX

SPEC: MIL-P-85582T1

MANF: DEFT
LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	1.88	.19	.46	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62814 COATING PRIMER/ENAMEL TFE GID: AUCNXX

MANF: SIERRACIN/HARRISON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	600	72	450	0.002	0	20

60960 COATING PROTEXOCOTE M70 GID: AKXXXX

MANF: THERMO COTE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.005		00.42	12.00	T MOD
X	1	025.9	014.3	0.005		02.34	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005491 2

60960 COATING PROTEXOCOTE M70 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.006	0.010		01.70	NONE
A	1	030.0	009.0	0.006	0.010		01.60	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	B	00019.82	1H-70F- 4H-120F-

TOXICITY

64440 COATING PT111 LACQUER GID: ASXXXX

MANF: PROD TECHNIQUES SPEC: TT-L-32

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.039	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64441 COATING PT401 RESIN GID: AKXXXX

MANF: PROD TECHNIQUES SPEC: MIS-13865 T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.95	.07	.18	.25H-46F- .25H-151F- 1.5H-250F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

20177 COATING PT401 RESIN/PT402 PRIMER GID: ATBGXX

MANF: PROD TECHNIQUES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	X	00006.45	SEE MFG & TEST DC

TOXICITY

06544 COATING PT404A GID: AKXXXX

MANF: PROD TECHNIQUES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002			05.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.73	.54	.54	72H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

20254 COATING PT750/PT402 PRIMER GID: AKXXXX

MANF: PROD TECHNIQUES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	10.96	.01	.00	24H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00003.38	4H-70F- 24H-150F-

TOXICITY

60426 COATING PTFE DISPERSION GID: AUCNXX

MANF: DUPONT

....NO TEST DATA AVAILABLE....

05773 COATING PYRALENE C GID: AKXXXX

MANF: SPEC: MIL-I-46058XY

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005492 4

20109 COATING PYRE ML GID: ALXXXX
MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.61	.05	.00	72H-302F-0psiaVACUUM

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62075 COATING PYROCOAT 565 (INORGANIC) GID: AKXXXX
MANF: AREMCO PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE
A	MMH
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60433 COATING PYROLAC P123 GID: AKXXXX
MANF: BENTLEY HARRIS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.56	.01	.00	SEE TEST REPORT

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20899 COATING PYROMARK 2500 HE BLACK GID: AKXXXX
MANF: BIG 3 SPEC: MB0125-063

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.2E-6	.23	.18	.09	SEE TEST REPORT

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05430 COATING PYROMARK HE GID: AKCKXX
MANF: BIG 3 SPEC: MB0125-063

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.40	.03	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05809 COATING QR43117X4-176 CAT/SIL GID: AKCKXX
MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.017		00.00	00.00	NONE
A	1	023.8	014.5	0.017			01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.90	.53	.00	.67H-167F-

ODOR

RT	RT WEIGHT	CURE
X	00003.98	.67H-167F-

TOXICITY

20514 COATING QUICK 65918 GID: AUXXXX
MANF: SEARS ROEBUCK & CO SPEC: ST47P892

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
X	00008.42	48H-70F-

TOXICITY

61987 COATING RC9108 4334-112 WHITE GID: ATAAXX
MANF: PENNWALT CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	24H-70F-

ODOR

RT	RT WEIGHT	CURE
A	V 00009.92	24H-70F-

TOXICITY

Information Handling Services, 2000

61987 COATING RC9108 4334-112 WHITE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					24H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
		24H-70F-

60707 COATING RC9108 EPOXY GID: ATBGEF

MANF: PENNWALT CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	100.0	014.7	0.002	0.250	00.00	00.00	NONE
I	1	100.0	014.7	0.003	0.003	00.83	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00004.17	24H-70F-

63321 COATING REFSET GID: AKXXXX

MANF: RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.055	0	20

05497 COATING REFSET L3203-6 GID: AKDEXV

MANF: RAYBESTOS-MANHATTAN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.39	.08	.26	120H-46F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	K 00043.02	

62863 COATING REFSET RL4389 GID: DPDBXX

MANF: RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.001	0	20

05734 COATING REFSET RL4389 CRYO-INSULATION GID: AKDEXX

SPEC: MB0120-065

MANF: RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		01.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.8E-7	6.54	.05		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	X 00007.18	SEE TEST REPORT

60115 COATING RESIN EPOXY GID: AKBGXX

SPEC: MIL-R-47252

MANF:

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.03	.00	.00	2H-176F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05986 COATING RESIN LIQUID TYPE MC6 GID: AKXXXX

MANF: MICA CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00001.48	.25H-70F-
		.08H-275F-

MSFC-HDBK-527 REV F 9999942 0005494 8

Information Handling Services, 2000

60807 COATING RK692 GID: AKXXXX

MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.34	.35	.00	1H-194F- 1H-572F- 1H-356F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05496 COATING RK692 PYRE ML GID: AKXXXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.001	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.001	0.003	00.00	00.00	NONE
A	1	030.0	010.0	0.003	0.010	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	B 00002.91	1H-420F-

TOXICITY

02096 COATING RTV 11/T12 SILICONE GID: BDCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.005	0.003		04.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.72	.15	.00	19440H-77F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

69812 COATING RTV DC Q36077 ABLATIVE/EPON 828/EPOCAST 951

MANF: DOW CORNING/SHELL CHEMICAL/FURANE
STRUCTURAL COMPOSITES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.045	01	06
X	MECH	14.7	10	-297	0.095	01	01
X	MECH	14.7	10	-297	0.145	01	01
X	MECH	50	20	-150	0.095	00	20
C	MECH	50.0	35	-150	0.045	00	20

60196 COATING RUBBER HYPALON NOC GID: AKDUXX

SPEC: USB-MS-5001

MANF: GACO WESTERN INC

....NO TEST DATA AVAILABLE....

20374 COATING RUSTOLEUM GID: AKXXXX

MANF: RUSTOLEUM

....NO TEST DATA AVAILABLE....

60717 COATING RUSTOLEUM X60 GID: AUXXXX

MANF: RUSTOLEUM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.003		05.60	NONE
B	1	033.0	014.3	0.003	0.003		07.90	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	2.99	.34		24H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
A	X 00013.23	24H-70F- 24H-150F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005495 T

05314 COATING S13 GLO THERMAL CONTROL SILICONE GID: AKXXXX

MANF: IITRI

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.42	.10	.00	48H-70F- 16H-250F-0psiaVACUUM

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60286 COATING S13-707 EPOXY GID: AUBGXX

MANF: DESOTO

....NO TEST DATA AVAILABLE....

06246 COATING S954-207 TEFLON GID: AKCNXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		02.00	NONE
A	1	030.0	010.4	0.001	0.003		01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.1E-6	1.50	.29	.40	.08H-70F- .5H-325F-

ODOR

RT	RT WEIGHT	CURE
A	B 00005.14	.08H-70F- .5H-325F-

TOXICITY

06584 COATING SCOTCHGARD EC4101-C16 GID: AKEFXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		00.80	NONE
A	1	025.9	014.3	0.001			01.10	NONE
A	1	033.0	014.3	0.001			01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-7	24.89	3.11		168H-70F-

ODOR

RT	RT WEIGHT	CURE
A	X 00000.14	168H-70F-

TOXICITY

64203 COATING SCOTCHGARD FC326 GID: AKXXXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.9E-6	12.07	.90	.13	48H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06368 COATING SEALER POLYURETHANE/EPOXY GID: ATXXXX

....NO TEST DATA AVAILABLE....

20073 COATING SEMIGLOSS BLACK GID: ATXXXX

....NO TEST DATA AVAILABLE....

05876 COATING SEMIGLOSS ENAMEL ZN/CR04 GID: ATAOAH

MANF: AMERICAN AEROSPACE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	X 00005.10	

TOXICITY

05895 COATING SERMETEL TW GID: AKXXXX

MANF: TELEFLEX INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.6E-6	.56	.26		.25H-175F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005496 1

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DATE: 12/23/88
NON-METALS BY DESIGNATION

05895 COATING SERMETEL TW (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					.5H-650F-
					1.5H-999F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE

60588 COATING SF-X-HARDCOAT ANTISCRATCH GID: AKXXXX

MANF: RESART

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.060			00.80	MOD
X	1	025.9	014.3	0.060		00.04	12.30	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.6E-6	.18	.00	.14	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00009.85	

60589 COATING SHC1200 HARDCOAT GID: AKXXXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.059			00.20	MOD
X	1	025.9	014.3	0.059			10.00	MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.6E-6	.15	.00	.12	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00010.10	

61252 COATING SILCARB/CERAMIC AB312 FAB

....NO TEST DATA AVAILABLE....

06315 COATING SILCARB/POLYETHYLENE GID: BBHOCK

MANF: BUEHLER LTD
N L INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.006			00.10	NONE
C	1	020.9	014.7	0.006		04.00	12.00	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.2E-6	.38	.11	.00	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05009 COATING SILICONE GID: AKCKXX

....NO TEST DATA AVAILABLE....

05994 COATING SILICONE (INORGANIC) GID: AKXXXX

....NO TEST DATA AVAILABLE....

06601 COATING SILICONE BLACK GID: ATXXXX SPEC: MA0105-331

MANF: ROCKWELL
SWS SILICONES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.04	.36	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

61016 COATING SILICONE BLACK VHT SP102 GID: ATCLXX

MANF: SPEREX CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

61016 COATING SILICONE BLACK VHT SP102 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.77	.05	.19	168H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

06593 COATING SILICONE GLASS/TETRABRN FIL GID: AKCKXX

MANF: LOCKHEED
SWS SILICONES

SPEC: MB0115-022
MB0130-175

MB0115-029

....NO TEST DATA AVAILABLE....

61233 COATING SILICONE JUNCTION R6101 GID: AMCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.017	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.2E-7	1.16	.62		1H-158F- 2H-300F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
B	00024.41	SEE TST RPT

62781 COATING SILICONE PV100 WHITE GID: AKCKXX

MANF: VITAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003	0.020	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	22.01	1.39	.00	24H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

06407 COATING SILICONE RED VHT SP109 GID: ATCLXX

....NO TEST DATA AVAILABLE....

80036 COATING SILICONE SEA200G ADHES GID: AKCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.010			01.90	NONE
A	1	020.9	014.7	0.125			01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.132	01	01
C	MECH	14.7	35	-314	0.131	00	20
I	MECH	50	72	-150	0.131	00	20
I	MECH	50	72	80	0.132	00	20

20690 COATING SILICONE SR80 RESIN GID: AKCKXX

MANF: GENERAL ELECTRIC

SPEC: SVHS 8511

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	100.0	019.0	0.001	0.125	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	00804.02	

60493 COATING SILICONE VESTAR Q9-6503 GID: AKCKHK

MANF: DOW CORNING

SPEC: ST46C1155

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		00.70	NONE
A	1	030.0	009.0	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.39	.04	.00	5H-300F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A B	00001.95	.5H-300F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005498 5

DATE: 12/23/88
NON-METALS BY DESIGNATION

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

20795 COATING SILICONE WHITE PT805 GID: ATCKXX

MANF: PROD TECHNIQUES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		01.00	NONE
A	1	030.0	010.4	0.001	0.003		00.90	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

TOXICITY

RT	RT	WEIGHT	CURE
	B	00017.08	1H-350F-

06480 COATING SILICONE WHITE VHT SP101 GID: ATCLXX

MANF: SPEREX CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003	00.00	00.00	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.29	.01	.00	.25H-70F- .25H-250F- 1H-601F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

TOXICITY

RT	RT	WEIGHT	CURE
No test data			

06002 COATING SILICONE XRTV6343 GID: ATXXXX

....NO TEST DATA AVAILABLE....

64442 COATING SILICONE/PRIMER GID: AUCKXX SPEC: MC7994-03 MC8006-01

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.060		00.30	NONE
A	1	020.9	014.7	0.001	0.075		03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06185 COATING SLIP RESISTANT POLYURETHANE GID: AKXXXX SPEC: MB0125-079

MANF:

....NO TEST DATA AVAILABLE....

62389 COATING SOLAR ABSORBER ECP2200 GID: ATXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002	0.003	00.00	00.00	NONE
A	1	025.9	014.3	0.001			00.00	NONE
A	1	030.0	010.0	0.002	0.003	00.00	00.00	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

TOXICITY

RT	RT	WEIGHT	CURE
A	B	00007.92	.12H-70F- 4H-400F-

06426 COATING SOLITHANE 113/300 GID: AKXXXY SPEC: MB0125-072

MANF: THIOKOL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.009			03.10	MOD
X	1	025.9	014.3	0.025	0.003		04.80	MOD
X	1	030.0	009.0	0.025	0.003		04.30	LARGE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.21	.00	.00	504H-70F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

TOXICITY

RT	RT	WEIGHT	CURE
No test data			

63303 COATING SOLITHANE 113/300/CABOSIL GID: ALXXXX

MANF: THIOKOL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.37	.01	.00	16H-158F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00010.40	

62491 COATING SOLITHANE C113-300/DC3140 GID: ALCQDP

MANF: DOW CORNING
THIOKOL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.152		00.07	12.00 T	MOD
X	1	025.9	014.3	0.172		00.30	08.40	MOD
X	1	025.9	014.3	0.202			05.90	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

00172 COATING SS4004 SS4004 SILANE GID: AUCKXX

MANF: GENERAL ELECTRIC

SPEC: MB0125-038

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.005	0.000	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	22.67	7.87	.00	24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00000.76	720H-70F-

05000 COATING SS4155 SILANE GID: AUCKXX

MANF: GENERAL ELECTRIC

SPEC: MB0125-050 ST47P122-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	030.0	010.0	0.005	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.001	0.003	00.00	00.00	NONE
A	1	100.0	020.2	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	22.51	.05	.00	1H-46F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00001.55	24H-70F-
		24H-70F-

60176 COATING SS4171 SILANE GID: AUXXXX

MANF:

SPEC: STW5-2858

....NO TEST DATA AVAILABLE....

05015 COATING SUPER KOROPON 515-700 GID: AUBGXX

MANF: DESOTO

SPEC: MB0125-055

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	10.66	.04	.21	24H-70F-
					4440H-70F-
					1512H-70F-
					5904H-70F-
					2928H-70F-
					7368H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00007.96	24H-150F-

61133 COATING SUPER KOROPON/LATEX433495 GID: ATBGAC

MANF: DESOTO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00017.70	24H-70F-TWO COATS OF KOROPON WERE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005500 T

61133 COATING SUPER KOROPON/LATEX433495 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR

RT	RT WEIGHT

TOXICITY

CURE
APPLIED WITH CURE AFTER EACH COAT.
24H-150F-BOTH COATS WAS THEN CURED.
THE SUBSTRATE WAS CROSS-HATCHED WITH SAND PAPER AND WIPED WITH A DAMP TOWEL, AND AIR DRIED.
24H-70F-TWO COATS OF LATEX PAINT 4334-95 WAS APPLIED LIGHTLY WITH A FINE BRISTLED BRUSH.

62038 COATING SYNKOTE 71976 BLUE GID: ATXXXX

MANF: TELE-MEASUREMENTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.017		00.37	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61167 COATING TAPE PRIMER 81 GID: AUXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002	0.003		02.20	NONE
C	1	033.0	014.3	0.002	0.003	00.67	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	7.43	2.89		48H-70F- 24H-150F-

ODOR

RT	RT WEIGHT
X	X 00005.61

TOXICITY

CURE
48H-70F-
24H-150F-

06261 COATING TECFLUOROCOTE X4 TEFLON GID: AKCOXX

....NO TEST DATA AVAILABLE....

05614 COATING TEFLON INFUSED GID: AKMABP

SPEC: MB0125-075

MANF: ENGINEERED DEVICES
GENERAL MAGNAPLATE
NIMET IND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.064		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.9E-7	4.11	.05		

ODOR

RT	RT WEIGHT
A	V 00007.83

TOXICITY

CURE

65485 COATING TEMP CONTROL POLYURETHANE/AL GID: AKXXXX

SPEC: MB0125-040

MANF: SIKKENS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001			01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	6.57	.45	.27	168H-70F-

ODOR

RT	RT WEIGHT
No test data	

TOXICITY

CURE

06032 COATING TEMPILAQ GR800 GID: AKXXXX

MANF: BIG 3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		00.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005501 1

06032 COATING TEMPILAQ GR800 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-6	5.07	.01	.64	24H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

02698 COATING TFE 1 COAT GRAY GID: AKCNXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	275	72	-297	0.003	0	20
B	PNEU	400	70	150	0.003	0	20
B	MECH	400	72	150	0.003	0	20

05224 COATING THERMAL CONTROL POLYURETHETHANE GID: AKXXXX

....NO TEST DATA AVAILABLE....

63874 COATING TOPCOAT YELLOW GID: AKXXXX

MANF: SHERWIN WILLIAMS

SPEC: MIL-C-83286 MIL-P-23377
MSFC SPEC 671

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	B	2160H-70F-

62779 COATING TRAIL CHEM PRIMER 20464-66 GID: AUBGXX

MANF: ODETICS INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.003			06.30	NONE
I	1	025.9	014.3	0.003		00.46	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.2E-6	3.14	.31	.40	72H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	X 00020.67	

65076 COATING TRITHERM 981 WIRE ENAMEL GID: AKXXXX

MANF: P D GEORGE CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.0E-6	1.97	.02	1.68	2H-400F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

62097 COATING TUFF-HYDE TEFLON GID: AKCNXX

MANF: HYDE PARK CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	7.6E-7	7.08	1.23		1H-70F- 168H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00000.71	1H-70F- 168H-70F-

62782 COATING TURCO T6094 BLACK GID: AKXXXX

MANF: TURCO PROD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7			00.10	10.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60202 COATING TURCO T6109 WHITE GID: AKXXXX

MANF: TURCO PROD

SPEC: STW5-2939

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005502 3

DATE: 12/23/88
NON-METALS BY DESIGNATION

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

60202 COATING TURCO T6109 WHITE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.250		00.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63428 COATING TURCO T6109/ELECTRODAY 500

MANF: TURCO PROD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.375	0.125	00.09	07.50	NONE
I	1	020.9	014.7	0.540		00.09	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20156 COATING TYROLIT #GED-0 OPTICAL

MANF: TYROLIT CORP

....NO TEST DATA AVAILABLE....

60218 COATING TYSEAL 22W73 WHITE GID: AKXXXX

MANF: MAGNA CTNG & CHEM

....NO TEST DATA AVAILABLE....

05644 COATING UNICOAT 2081-31A EPOXY GID: ALBHXX

MANF: AMICON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.010	00.00	00.00	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.31	.11	.00	24H-70F- 1H-356F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

TOXICITY

RT	RT	WEIGHT	CURE
A	X	00000.80	.5H-70F- 8H-220F-

20354 COATING UNICOAT 501

MANF: AMICON

....NO TEST DATA AVAILABLE....

20209 COATING URALANE 5750 A/B GID: ALCOBG

SPEC: MIL-I-46058 MIL-I-46058C

MANF: FURANE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.065		00.14	11.40	T MOD
I	1	030.0	009.0	0.125		00.20	12.00	T NONE
C	2	030.0	010.0	0.008		00.00	00.00	NONE
C	1	030.0	010.0	0.008		00.40	12.00	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.84	.05		1H-70F- 9H-150F- 24H-70F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

TOXICITY

RT	RT	WEIGHT	CURE
	X	00020.35	.5H-70F-30M-RT/1H-RT/9H-149F 9H-149F- 1H-70F-30M-RT/1H-RT/9H-149F 9H-149F- 9H-149F-30M-RT/1H-RT/9H-149F

62237 COATING URALANE 5753/CIRCUIT BRD GID: ALCQBG

MANF: M & T CHEMICALS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.117		00.11	11.40	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

TOXICITY

RT	RT	WEIGHT	CURE
A	B	00010.12	9H-149F-

Information Handling Services, 2000

05972 COATING URAMET 4-1W-12 #100 GRIT GID: AKCQXX

MANF: ADVANCED COATINGS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.006	0.032	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.0E-6	.96	.04		

ODOR

RT	RT	WEIGHT	CURE
A	A	14.21	

TOXICITY

80204 COATING URETHANE 03W127

MANF: DEFT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	6.07	.07	.89	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

61997 COATING URETHANE 17875-5008 WHITE GID: ATAGXX

MANF: ALL METAL PROCESSING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003		04.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
U	2.6E-6	32.41	.23		48H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	X	00007.32	48H-70F-

TOXICITY

62783 COATING URETHANE 550/5007 BASE GID: AKCQXX

MANF: FUTURA COATING INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.040			00.50	NONE
X	1	020.9	014.7	0.040			02.70	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65364 COATING URETHANE AP4004/AP4154 GID: AKDUXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.100			01.30	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.6E-6	2.96	.38	.88	24H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

61066 COATING URETHANE ASMBY GID: ATCQBG

MANF: U S COATINGS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
C	2	025.9	014.3	0.003	0.003	00.00	00.00		NONE
C	1	025.9	014.3	0.003	0.003	00.52	12.00	T	NONE
A	1	025.9	014.3	0.002	0.010		01.50		SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	V	00019.58	1H-70F-
			24H-70F-

TOXICITY

62382 COATING URETHANE MS470 GID: ALCQXX

MANF: MILLER STEPHENSON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	B	00003.01	.5H-70F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005504 7

62954 COATING URETHANE ON 1/16 AL FOIL GID: AKCQFK

MANF: TELEDYNE BROWN ENG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.063			02.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

61517 COATING VARNISH 961 GID: AKXXXX

MANF: P D GEORGE CO

SPEC: MIL-V-1137TMGCB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003		02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.6E-7	8.85	1.14		.75H-275F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00007.50	.75H-275F-

62202 COATING VARNISH GLPT RED GID: ATXXXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		02.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.0E-6	9.44	.00		168H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00004.94	168H-70F- 24H-150F-

69831 COATING VARNISH HI-THERM BB252 BLACK BAKING GID: ASXXXX

MANF: DOLPH COMPANY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	2.93	.71	.22	.22H-70F- 2H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

60220 COATING VINYL UTC4005-30301 GID: AKXXXX

MANF: IOWA PAINT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.36	.04		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

60221 COATING VINYL UTC4005-30301 WHITE

....NO TEST DATA AVAILABLE....

20460 COATING VISANEL NON-GLOSS GID: ATXXXX

....NO TEST DATA AVAILABLE....

62785 COATING VITON B50/ZIPPER NOMEX GID: AKBVXX

MANF: GOODYEAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.025			03.20	SMALL
A	1	025.9	014.3	0.024			02.10	SMALL
A	1	025.9	014.3	0.025			02.70	SMALL
A	1	030.0	009.0	0.025			01.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

62784 COATING VITON/CLAY ON FAB NYLON GID: AKXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.015			04.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

Information Handling Services, 2000

20214 COATING WASH PRETREATMENT GID: AKXXXX
MANF: KOPPERS CO SPEC: MIL-P-15328

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	X	00001.07	168H-70F- 24H-150F-

65206 COATING WATER BASE PRIMER GID: AUXXXX
MANF: DEFT SPEC: MIL-P-85582T1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.0E-6	1.22	.41	.32	168H-70F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

60907 COATING WATER-ACRYLIC ENAMEL BLUE GID: ATAAXX
MANF: MOBIL OIL CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002			00.90	NONE
A	1	023.8	014.5	0.003			00.29	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
X	X	00006.96	24H-70F-

05642 COATING WATERPROOF RSI TILES GID: AKXXXX
....NO TEST DATA AVAILABLE....

61663 COATING WD40
MANF: ROCKET CHEM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
S	5.0E-5				

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

65081 COATING WHITE EPOXY/H2 GID: ATBGXX
MANF: SHELL CHEMICAL SPEC: SVHS 9656T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.010		00.00	00.00	NONE
C	1	025.9	014.3	0.010		00.40	12.00	T NONE
C	2	030.0	010.0	0.010		00.00	00.00	NONE
C	1	030.0	010.0	0.010		00.60	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	4.36	.37	.53	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	K	00022.60	

62193 COATING WONDER/PRIMER 442-3B GID: AKXXXX
MANF: OIL CENTER RESEARCH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	X	00000.50	24H-70F-

05763 COATING X300 EPOXY GID: ABBGXX
MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003		01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	9.15	.09	.00	8H-212F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	B	00006.31	4H-212F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005506 0 ■

DATE: 12/23/88
NON-METALS BY DESIGNATION

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

05962 COATING X75207-66 EPOXY/ENAMEL GID: ATBGXX

MANF: TRAIL CHEMICAL CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003		01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.0E-7	.39	.03		24H-70F- .08H-400F-

ODOR

RT	
A	X

TOXICITY

RT WEIGHT	CURE
00001.22	.08H-400F-

62144 COATING XECOTE GID: AMXXXX

MANF: METEX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	8.4E-7	.27	.05		1H-140F-

ODOR

RT
No test data

TOXICITY

RT WEIGHT	CURE

61241 COATING XECOTE/OCF4190B WITH F017A GID: AMHLXX

MANF: METEX
OWENS CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	8.4E-7	.32	.08		1H-140F-

ODOR

RT
No test data

TOXICITY

RT WEIGHT	CURE

61242 COATING XECOTE/X389-7 TFE BETA GID: AMCNHL

MANF: DODGE
METEX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	8.4E-7	.15	.03		1H-140F-

ODOR

RT
No test data

TOXICITY

RT WEIGHT	CURE

05716 COATING XR5133 EPOXY GID: AKBGXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.43	.02	.00	.5H-300F-

ODOR

RT	
A	B

TOXICITY

RT WEIGHT	CURE
00023.70	.5H-300F-

60665 COATING XYLAN 1010 BLACK GID: ATCDCA

MANF: WHITFORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	400	10	-297	0.031	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.4E-6	3.40	.02	.64	3H-257F-

ODOR

RT
No test data

TOXICITY

RT WEIGHT	CURE

64867 COATING YELLOW 33798 PRIMER/EPOXY TOPCOAT

SPEC: MIL-C-83286 MIL-T-81772AT1
PR MIL-P-23377D

MANF: RANDOLPH PRODUCTS
SENTRY/EASTERN CHEMICAL LAC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	024.5	014.5	0.002	0.003	00.44	09.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
K

TOXICITY

RT WEIGHT	CURE

05542 COATING Z205 SERIES GID: ATXXXX

MANF: LORD CORP

NO TEST DATA AVAILABLE....

Information Handling Services, 2000

05022 COATING ZINC CHROMATE GID: AUAHXX

SPEC: MIL-P-8585 TT-P-1757

MANF: ANDREW BROWN
AUTOMOTIVE FINISHES
KOPPERS CO
U S PAINT LACQUER & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.040		00.00	00.00	NONE
A	1	023.8	014.5	0.001	0.003		01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.23	.22	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00002.75	168H-70F- 24H-150F-

05930 COATING ZINC RICH T1 C1 INORGANIC GID: AKHAXX

SPEC: KSC-SPEC F-0020

MANF:
....NO TEST DATA AVAILABLE....

05651 COLODIAL SILICA SPHERES (INOR) GID: DOHOHO

....NO TEST DATA AVAILABLE....

68373 COMALLOY 110-1520

MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

60991 COMB STYLING MARK IV GID: FCXXXX

MANF: CONAIR

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00087.70	

61244 COMPASS MAGNETIC FSN6605-846-7618 GID: EXXXXX

MANF: UNION INSTRUMENT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00126.85	

61101 COMPONENT BOARDS DC 1-2577 GID: EZXXXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.080			01.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00020.10	

65135 COMPOSITE 5245C RESIN/IMG FIBR GID: BBFVXX

MANF: HERCULES
NARMCO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-6	.33	.01	.13	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

63429 COMPOSITE DACRON/MYLAR/NYLON GID: BBXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.125		00.18	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005508 4

63429 COMPOSITE DACRON/MYLAR/NYLON (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.300	0.125	00.12	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

06304 COMPOSITE EPOXY FIBERGLS A8514 GID: BBFVBG

MANF: NUPLA CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	.40	.02	.07	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63433 COMPOSITE GLASS/AL/934 RESIN GID: BBXXXX

MANF: LORD CORP

SPEC: STM-K-796

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.088			00.50	NONE
B	1	020.9	014.7	0.088		00.10	06.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62458 COMPOSITE KEVLAR/EPOXY WRAP GID: BBBGCD

MANF: BRUNSWICK

SPEC: SV767701

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	030.0	009.0			00.00	00.00	NONE
A	1	030.0	009.0			00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.2E-6	4.89	.09	1.24	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63775 COMPOSITE KEVLAR/VITON GID: BBJHXX

MANF: GOODYEAR

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	K 00076.75	

TOXICITY

62748 COMPOSITE NEOPRENE/NOMEX HT337 GID: BBDBBV

MANF: EH33

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.110			03.70	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62749 COMPOSITE NEOPRENE/POLYESTER GID: BBDBCB

MANF: EH33

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.120			06.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05538 COMPOSITE REINFORCEMENT GID: BBBGXX

MANF: BRUNSWICK

SPEC: BMS-161-756

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.217		00.59	02.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.2E-6	2.42	.03		

ODOR

RT	RT WEIGHT	CURE
A	K 00020.19	

TOXICITY

63432 COMPOSITE SRB THERMAL CURTAIN GID: BBXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005509 6

63432 COMPOSITE SRB THERMAL CURTAIN (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.250			02.00	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

62750 COMPOSITE VITON B50/DACRON GID: BBDEXX

MANF: MCDONNELL DOUGLAS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.100			02.50	NONE
A	1	025.9	014.3	0.100			03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62751 COMPOSITE VITON B50/NOMEX 426 GID: BBDEBX

MANF: MCDONNELL DOUGLAS
MDAC-WD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.100		00.00	00.00	NONE
A	1	023.8	014.5	0.110			01.00	NONE
A	1	025.9	014.5	0.100		00.00	00.00	NONE
A	1	025.9	014.3	0.110			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62752 COMPOSITE VITON B50/NOMEX RF41 GID: 4BBDEB

MANF: GOODYEAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.085		00.00	00.00	NONE
A	1	023.8	014.5	0.110			02.00	SMALL
A	1	023.8	014.5	0.090		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62754 COMPOSITE VITON B50/POLYESTER GID: BBDECB

MANF: GOODYEAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.080			04.00	SMALL
A	1	023.8	014.5	0.090			03.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63785 COMPOSITE VITON E60C/NOMEX HT426 GID: EXXXXX

SPEC: MIL-R-83248T2C1

MANF: DUPONT
S/N ID221290
STM 0699-01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00074.90	

62753 COMPOSITE VITON/POLYEST DY793 GID: BBDECB

MANF: GOODYEAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.110			02.20	SMALL
A	1	025.9	014.3	0.110			04.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62340 COMPOUND ACROSONIC 100 GEL GID: AWEKXX

MANF: PARKER LABORATORIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00173.14	

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005510 2 ■

06435 COMPOUND ANTI-ICING DMSO/H20/PECTIN GID: AWXXXX
MANF: ROCKWELL

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.250	0.010		02.00	NONE	No test data		No test data							

20783 COMPOUND ANTI-SEIZE METHOCEL/SILICONE CARB
....NO TEST DATA AVAILABLE....

69802 COMPOUND ANTI-SEIZE ROYCO 44
MANF: ROYAL LUBRICANTS
....NO TEST DATA AVAILABLE....

65389 COMPOUND E4-7.25 GLASS FILLED/GREEN GID: AWIAXX
MANF: PYLE NATIONAL CO

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	2.9E-6	.42	.00	.14	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

65386 COMPOUND E4-7.68/GLASS/DARK GREY GID: AWIAXX
MANF: PYLE NATIONAL CO

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	2.9E-6	.11	.00	.04	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

65385 COMPOUND E4-7.70 GLASS FILLED/BLACK GID: AWIAXX
MANF: PYLE NATIONAL CO

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	2.9E-6	.51	.00	.17	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

65388 COMPOUND E4-7.71 GLASS FILLED/BLACK GID: AWIAXX
MANF: PYLE NATIONAL CO

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	2.9E-6	.07	.00	.03	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

65387 COMPOUND E4-8.97 BLUE GID: AWEGXX
MANF: PYLE NATIONAL CO

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	2.9E-6	.35	.12	.04	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

61754 COMPOUND EPOXY 8013R/8012H GID: AWBGXX
MANF: WILMINGTON CHEM CO

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	023.8	014.5	0.010	0.003		11.00	NONE	No test data		No test data							
C	1	023.8	014.5	0.010	0.003	00.33	12.00	T SMALL										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	2.0E-6	6.61	.07		24H-70F- 4H-194F-

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
	V 00017.91	24H-70F- 4H-194F-

06519 COMPOUND HEAT SINK SILICONE VB GID: DBCKXX
MANF: GENERAL ELECTRIC SPEC: MB0110-005T3

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
[illegible]	[illegible]	025.0	014.3	0.010	0.003		00.50	NONE	No test data		No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005511 4

06519 COMPOUND HEAT SINK SILICONE VB (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.4	0.010	0.003		00.70	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.16	.09	.01	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00019.76	

06116 COMPOUND HEAT SINK THERMAL 120 GID: AXXXXX

MANF: WAKEFIELD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00021.69	

06248 COMPOUND HEAT TRANSFER G642 SILICONE GID: AYCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.050	0.003		01.80	NONE
A	1	030.0	009.0	0.055	0.003		03.20	NONE

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.50	.07	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00017.88	

60420 COMPOUND JACKET

....NO TEST DATA AVAILABLE....

63324 COMPOUND LEAK TEST GID: AWXXXX

MANF: AMERICAN GAS & CHEMICAL

SPEC: MMS-Y-824

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

STM-Y-824

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297		0	20
X	MECH	14.7	10	-297		0	20

62876 COMPOUND LEAK TEST MMSY824C100 GID: AWXXXX

MANF: AMERICAN GAS & CHEMICAL

SPEC: MSFC 384

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-220		0	20

62886 COMPOUND LEAK TEST N727C GID: AWXXXX

MANF: AMERICAN GAS & CHEMICAL

SPEC: MMS-Y-824C100

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-220	0.062	0	20

80032 COMPOUND LEAK-TEC 160X GID: AWXXXX

MANF: AMERICAN GAS & CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	10000	72	75	0.050	00	20
B	MECH	5000	72	75	0.050	00	20

80033 COMPOUND LEAK-TEC FORMULA #277 HE GID: CACQXX

MANF: AMERICAN GAS & CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	10000	72	75	0.050	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005512 6

80033 COMPOUND LEAK-TEC FORMULA #277 NE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	5000	72	75	0.050	00	20

06314 COMPOUND PQ HEAT SINK GID: AYXXXX

MANF: AMERICAN OIL & SUPPLY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.0E-6	4.13	3.13	.06	

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

64269 COMPOUND TA2417 SILICONE GID: AWCKXX

MANF: T A MFG CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.070			01.10	NONE

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.12	.02		

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

60446 COMPOUND THERMACOTE BLUE POLYBUTENE GID: BACEXX

MANF: THERMALLOY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-7	9.98	7.36		24H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
A	B 00015.09	24H-70F- 24H-150F-

TOXICITY

60874 COMPOUND THERMACOTE NOC SILICONE GID: BACKXX

MANF: THERMALLOY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3		0.003	00.00	00.00	NONE
A	1	033.0	014.3		0.003		02.00	NONE

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.12	.28	.00	

ODOR

RT	RT WEIGHT	CURE
A	B 00024.85	24H-70F- 48H-150F-

TOXICITY

62009 COMPOUND THERMACOTE PINK GID: BAXXXX

MANF: THERMALLOY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3		0.003	00.80	12.00	T NONE

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.19	2.11		24H-70F- 48H-150F-

ODOR

RT	RT WEIGHT	CURE
A	B 00030.46	24H-70F- 48H-150F-

TOXICITY

62008 COMPOUND THERMACOTE POLYBUTENE GID: BACEXX

MANF: THERMALLOY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.005	0.003	00.79	12.00	T NONE

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	11.85	3.95		24H-70F- 48H-150F-

ODOR

RT	RT WEIGHT	CURE
A	B 00016.21	24H-70F- 48H-150F-

TOXICITY

Information Handling Services, 2000

62283 COMPOUND THERMAL CONDUCTIVE URETHANE SMRD 902 GID: AWCQXX
MANF: GENERAL ELECTRIC SPEC: 17A4629 T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.200			01.20	MOD
X	1	030.0	009.0	0.200			00.80	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00020.36	

TOXICITY

62306 COMPOUND UNISET A316-7 EPOXY GID: AWBGGL
MANF: AMICON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.28	.02	.20	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64301 COMPOUND URALANE/GLASS 12887-547 GID: AWIAXX
MANF: FURANE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.4E-6	1.51	.00	.06	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64295 COMPOUND URALANE/GLASS 12887-556 GID: AWIAXX
MANF: FURANE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.4E-6	1.48	.00	.05	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64292 COMPOUND URALANE/GLASS 5753LV A1 GID: AWIAXX
MANF: FURANE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.4E-6	.73	.00	.06	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64296 COMPOUND URALANE/GLASS 5753LV B1 GID: AWIAXX
MANF: FURANE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.4E-6	1.44	.04	.06	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64297 COMPOUND URALANE/GLASS 5753LV C1 GID: AWIAXX
MANF: FURANE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.4E-6	1.57	.02	.06	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64299 COMPOUND URALANE/GLASS 5753LV V1 GID: AWIAXX
MANF: FURANE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.4E-6	1.02	.01	.07	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64298 COMPOUND URALANE/GLASS 5753LV X1
MANF: FURANE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.4E-6	1.36	.00	.08	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005514 T

64300 COMPOUND URALANE/GLASS 5753LV X1 GID: AWIAXX
MANF: FURANE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.4E-6	1.18	.01	.07	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

65632 CONCRESIVE 1001
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65633 CONCRESIVE 1001 LPL
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65658 CONCRESIVE 1442
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65647 CONCRESIVE 3012
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

65654 CONCRESIVE AEX 1482-0
MANF: ADHESIVE ENGINEERING CO
....NO TEST DATA AVAILABLE....

64854 CONFIG COMPOSITE SHUTTLE SUIT GID: FGXXXX
MANF: ILC DOVER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.111			00.60	MOD
X	1	100.0	020.2	0.111		00.26	05.60	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	0.0E-6	1.10	.14		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00129.03	

64828 CONFIG NYLON VELCRO/COTTON GID: COFSBV
MANF: VELCRO CORP

SPEC: MB0130-105
MIL-T-43636

MIL-C-83286

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.250			04.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64849 CONFIG NYLON VELCRO/COTTON COF GID: SBV
MANF: VELCRO CORP

SPEC: MB0130-105
MIL-T-43636

MIL-C-83286

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.250			06.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62755 CONFIG PWB/COATED WITH PR1568 GID: FBXXXX
MANF:

SPEC: MIL-I-43553 INK

MIL-M-83436

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.310			01.40	NONE
X	1	050.0	014.5	0.310		00.06	06.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005515 1

64855 CONFIG SEE 06475/05325 GID: COBGGF

MANF: FIBERITE
HEXCEL

SPEC: MB0130-087T3C4 MB0130-135

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.681		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64803 CONFIG SEE05387/88/89/90/91/92 GID: FJCKMA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.058			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61591 CONFIG VITON RT876/THERMOFIT GID: EHDEXX

MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.256			03.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.43	.10	.00	.25H-257F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64834 CONFIG/SEE 20406/20579 GID: BFBVCQ

MANF: KENYON PIECE DYEWORKS
SOUTHERN MILLS

SPEC: ST12N084-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.025			01.20	NONE
A	1	030.0	009.0	0.025			01.60	NONE
I	1	033.0	009.0	0.025		00.35	11.50 T	NONE
A	1	040.0	009.0	0.025			02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62020 CONFIGURATION NOMEX/RTV GID: CKBVCK

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		020.9	006.7					NONE
		020.9	010.1					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64235 CONN MPE PROTECTIVE CAPS GID: BCXXXX

MANF: ITT CANNON

....NO TEST DATA AVAILABLE....

64236 CONN TERMINAL FUNCTION MODULES GID: BCXXXX

MANF: PRECISION CONNECTORS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
S	2.0E-6				

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61381 CONNECTOR 15-319D GID: BNCGXX

MANF: FISHER SCIENTIFIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5			00.05	12.00 T	MOD
X	1	023.8	014.5			00.08	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.17	.05		

ODOR

RT	RT WEIGHT	CURE
A	K 00011.93	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005516 3

61306 CONNECTOR 2001-5119-00 GID: BCXXXX
MANF: OMNI SPECTRA SPEC: OSM 241-2

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00002.03	

TOXICITY

61321 CONNECTOR 38108-24-61S GID: FCBXCK
MANF: DEUTSCH SPEC: LS41305-154

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00087.03	

TOXICITY

05897 CONNECTOR 40M MODIFIED GID: BCMACK
MANF: ITT CANNON SPEC: 40M39569REVCE04

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00140.14	

TOXICITY

60660 CONNECTOR 40M RECEPTACLE/PLUG GID: BCMACK
MANF: BENDIX SPEC: 40M38277/39565

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00089.81	

TOXICITY

85425 CONNECTOR CIRCUIT BOARD FR4 DOUBLE WIDTH FLIGHT WITH HUMISEL 1B31 ACRYLIC TYPE AR CONFORMAL COATING
MANF: MULTIWIRE/COLUMBIA TECH CORP SPEC: RAU-ADT-16A.2.1-4033[2P440-874

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.100		00.03	02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63863 CONNECTOR CONTACT 7219 GID: FCXXXX
MANF: MATRIX SCIENCE CORP SPEC: ST180-12-16B

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00038.02	

TOXICITY

64214 CONNECTOR D-SUB DEM/DAM/DBM GID: BCXXXX
MANF: JAPAN AVIONICS CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00049.22	

TOXICITY

80211 CONNECTOR D-SUB ND101-50S-C ND101-50P-C GID: BCXXXX
MANF: JAPAN AVIATION ELECTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.600			02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	48.515	

TOXICITY

80133 CONNECTOR D-SUB ND101-9S-C/ND101-9P-C GID: BCXXXX
MANF: JAPAN AVIATION ELECTRONICS SPEC: NASDA-QTS-24308/101

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.600			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	25.492	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005517 5

63226 CONNECTOR DAP 280-35001-208 GID: BCXXXX
MANF: ITT CANNON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.450			01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62234 CONNECTOR DAP/GLASS FILLED GID: BCIAFW
MANF: ITT CANNON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.44	.00	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00018.25	

61237 CONNECTOR DM5623-37-37 PP GID: BCXXXX
MANF: DEUTSCH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.7E-7	.03	.01		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

64824 CONNECTOR DUCTORSEAL 6837/6838 GID: EZBGCN
MANF: DOUGLAS ENGINEERING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3				00.10	NONE
A	1	100.0	003.8				00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80207 CONNECTOR ELASTOMERIC ZEBRA STRIPS FSC-C-.002 PITCH GID: BCXXXX
MANF: FUJI RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.0E-6	.48	.11	.23	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

63896 CONNECTOR ELEC 13% GLASS/NYL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.62	.04	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00009.77	

61643 CONNECTOR ELEC 27473E8F35P GID: BCXXXX
MANF: BENDIX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00052.28	

64987 CONNECTOR ELEC 27499E10F99P GID: BCXXXX
MANF: BENDIX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00052.28	

65547 CONNECTOR ELEC 27508E12F35P GID: BCXXXX
MANF: BENDIX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	52.28	

64989 CONNECTOR ELEC 3476L10-S5 GID: BCXXXX
MANF: BENDIX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00052.28	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005518 7

60657 CONNECTOR ELEC DDM43W2SK52 GID: BCXXXX
MANF: ITT CANNON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00068.15	

85393 CONNECTOR ELEC DG123 GID: BCXXXX
MANF: DEUTSCH

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	025.9	014.3	1.250	00.25	
B	030.0	009.0	1.130	00.50	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.51	.07	.26	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	50.2	

64984 CONNECTOR ELEC G05D170A2BABL GID: BCXXXX
MANF: ITT CANNON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00068.15	

61250 CONNECTOR ELEC JT06A-8-65(300) GID: BCAQCK
MANF: BENDIX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00011.23	

60656 CONNECTOR ELEC M1K6-1-7-PH016 GID: BCXXXX
MANF: ITT CANNON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00068.15	

60655 CONNECTOR ELEC M1KM0-1-7-SH016 GID: BCXXXX
MANF: ITT CANNON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00068.15	

69889 CONNECTOR ELEC M24308/1-2 GID: BCXXXX
MANF: ITT CANNON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	9.80	

69879 CONNECTOR ELEC M24308/2-3 GID: BCXXXX
MANF: ITT CANNON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	14.94	

69878 CONNECTOR ELEC M24308/2-5 GID: BCXXXX
MANF: ITT CANNON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	24.69	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005519 9

69904 CONNECTOR ELEC M24308/4-3 GID: BCXXXX
MANF: ITT CANNON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	13.69	

64988 CONNECTOR ELEC PT06E-10-S5005 GID: BCXXXX
MANF: BENDIX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00052.28	

65327 CONNECTOR ELECT GLASS/PHENOLIC GID: BCXXXX
MANF: WEIDMULLER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	2.000			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.31	.01	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00021.98	

62049 CONNECTOR ELECT SILICONE RUBBER/CERAMIC GID: BCXXXX
MANF: MATRIX SCIENCE CORP

SPEC: MIL-C-005015 MS3450L36-1D MS3450L36-10SW

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	2.250		00.01	01.90	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.0E-7	.65	.21		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00408.66	

61249 CONNECTOR ELECTRIC GID: BCAQCK
MANF: DEUTSCH

SPEC: RTK06-8-7P

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00011.12	

80096 CONNECTOR ELECTRIC 84450 GID: FCXXXX
MANF: DEUTSCH

SPEC: MIL-C-38999

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
S	5.0E-5				

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

80097 CONNECTOR ELECTRIC G & HV GID: FCXXXX
MANF:

SPEC: MIL-C-38999

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
S	5.0E-5				

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

20644 CONNECTOR ELECTRICAL GID: BCXXXX
MANF: BENDIX

SPEC: HS 1550

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00017.01	

60704 CONNECTOR ELECTRICAL GID: FCBXCK
MANF: BENDIX

SPEC: JT06REIO-355408 LS41164-555

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005520 5

60704 CONNECTOR ELECTRICAL (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00012.01	

TOXICITY

60857 CONNECTOR ELECTRICAL GID: BCXXXX
MANF: ITT CANNON
SPEC: ME414-0611-0002 TBFH22950-73

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00269.45	

TOXICITY

61182 CONNECTOR ELECTRICAL GID: BCXXXX
MANF: ITT CANNON
SPEC: MS27506F10-2

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00007.19	

TOXICITY

61220 CONNECTOR ELECTRICAL GID: FCXXXX
MANF: BENDIX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.0E-6	.31	.06		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

61221 CONNECTOR ELECTRICAL GID: BCCKMA
MANF: ITT CANNON
SPEC: 40M38277REVE0#4

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	1.700			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00030.15	

TOXICITY

61222 CONNECTOR ELECTRICAL GID: BCCKMA
MANF: DEUTSCH
SPEC: 40M39569REVCE04

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	1.700			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00046.31	

TOXICITY

62413 CONNECTOR ELECTRICAL GID: BCXXXX
MANF: BENDIX
SPEC: MIL-C-38999 MS27473E12F985

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.50	.25	.00	

ODOR

RT	RT	WEIGHT	CURE
	B	00011.76	48H-250F-0psiaVACUUM

TOXICITY

62534 CONNECTOR ELECTRICAL GID: FCXXXX
MANF: BENDIX
PNJT00RP-10-99510051
PNJT06RP-10-9910051

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3				00.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00010.10	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005521 7

63530 CONNECTOR ELECTRICAL GID: FAXXXX

MANF: AMP INC
AQM
BENDIX
BURNDY
DEUTSCH
HUGHES AIRCRAFT
ITT CANNON
MALCO
NASA/GSFC
NASA/KSC
TIME ELECTRONIC WEST
TROMPETER

SPEC: 40M38277
G311P409-35-812
MIL-C-38999
MIL-C-5015
MS3475L12-10P
P/N CVA6R2D-15Z16

40M39569
MIL-C-28804
MIL-C-39012
MIL-C-83723
MSFC 40M39569

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.46	.11	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00019.10	

64120 CONNECTOR ELECTRICAL GID: BCXXXX

MANF: ITT CANNON

THERMAL VACUUM STABILITY

No test data

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00272.99	

61034 CONNECTOR ELECTRICAL 18-32 #4 GID: BCDPXX

MANF: BENDIX

SPEC: MIL-C-38999

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.470		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

MS27472-73

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61033 CONNECTOR ELECTRICAL 18-32P #1 GID: BCDPXX

MANF: BENDIX

SPEC: MIL-C-38999

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.470			00.10	NONE

FSC

RT	FLUID NAME
No test data	

MS27472-73

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60445 CONNECTOR ELECTRICAL 22541 GID: BCXXXX

MANF: AMP INC

SPEC: MIL-C-24308

THERMAL VACUUM STABILITY

No test data

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00010.88	

60705 CONNECTOR ELECTRICAL 73E GID: BCXXXX

MANF: ITT CANNON

SPEC: MIL-C-0038999
MS27473E24F35S

MS27473E24F35P

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.900		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.6E-6	.07	.07		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00112.40	

62706 CONNECTOR ELECTRICAL 97E GID: BCXXXX

MANF: BENDIX

SPEC: MIL-C-38999
MS27497E24F35S

MS27497E24F35P

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.900		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005522 9

62706 CONNECTOR ELECTRICAL 97E (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	8.0E-7	.25	.01		

ODOR

RT	RT	WEIGHT	CURE
	A	00097.76	

TOXICITY

61177 CONNECTOR ELECTRICAL PLUG GID: BCXXXX

MANF: DEFENSE DEPOT
ITT CANNON

SPEC: M83723-23R2015N MS3459L20-15P

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3				00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00072.57	

TOXICITY

69913 CONNECTOR ELECTRICAL SUBMINIATURE RECTANGULAR D/M RA2E12C0885M000 8241

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	21.5	

TOXICITY

64071 CONNECTOR INSERT SILICONE/RUBBER GID: BCDPXX

MANF:

SPEC: DPA C75-1 NLSOT20-35S

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0			00.04	00.35	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.87	1.64	.00	24H-347F-

ODOR

RT	RT	WEIGHT	CURE
	K	00022.27	

TOXICITY

20629 CONNECTOR JUNCTN CTV122E05/10 GID: BCXXXX

MANF: DEUTSCH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	V	00005.62	

TOXICITY

05213 CONNECTOR MALE-MC/ME414-0148 GID: BCXXXX

MANF: ITT CANNON

SPEC: DPKB-1015A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00131.10	

TOXICITY

61307 CONNECTOR MS2743E14F37PC GID: BCXXXX

MANF: ANVET ELECTRONICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00021.06	

TOXICITY

62094 CONNECTOR MS3112E14-19P GID: BCXXXX

MANF: BENDIX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5			00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-7	4.63	2.21		

ODOR

RT	RT	WEIGHT	CURE
X	A	00015.00	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005523 0

61312 CONNECTOR MS3456L20-15PW GID: FCXXXX
MANF: MARSHALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00059.35	

61518 CONNECTOR NB-CR-20 SPEC: MIL-C39029/4
MANF:
....NO TEST DATA AVAILABLE....

61520 CONNECTOR NB-CS-16 SPEC: MIL-C39029/5
MANF:
....NO TEST DATA AVAILABLE....

61519 CONNECTOR NB-CS-20 SPEC: MIL-C39029/5
MANF:
....NO TEST DATA AVAILABLE....

61521 CONNECTOR NB-GSP-16 SPEC: MS27488-16
MANF:
....NO TEST DATA AVAILABLE....

61522 CONNECTOR NB-GSP-20 SPEC: MS27488-20
MANF:
....NO TEST DATA AVAILABLE....

61646 CONNECTOR P/N 2075060 GID: FCXXXX
MANF: DATEL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	01259.58	

62191 CONNECTOR P/N 41203 PHENOLIC GID: FCXXXX
MANF: THERMOELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-6	.46	.00		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

61885 CONNECTOR PC BOARD 10-398050-1P GID: BDXXXX SPEC: MC414-0613-0004
MANF: BENDIX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00049.50	

61773 CONNECTOR PC BOARD DAP/ORLON GID: BEAQAK
MANF: ARMEL ELECTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.361		00.03	02.90	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.8E-6	.65	.00		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00043.08	

80037 CONNECTOR PC BOARD WTB90PR-7SY-X/WTB90SED-9SY-X GID: BCXXXX
SPEC: MIL-C-55302/59
MANF: AIRBORN INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.400			00.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005524 2

80037 CONNECTOR PC BOARD WTB90PR-7SY-X/WTB90SED-9SY-X (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	K	38.059	

80300 CONNECTOR PIN NUPAC 108/NYLAFIL G20/40 GID: BCXXXX

MANF: DART INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.375		0.03	04.25	LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	K	18.40	

85414 CONNECTOR PLASTIC WTB56SAD11SY-17

MANF: AIRBORN INC — SPEC: MIL-C-55302 — MIL-P-46174C40GE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.250		0.002	00.25	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62436 CONNECTOR PLIERS UTICA 529 GID: FCXXXX

MANF: UTICA — SPEC: ST20P1176-01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	K	00286.94	

20339 CONNECTOR POLYPROPYLENE #6151 GID: BCCQXX

MANF: NALGE DIV, SYBRON CORP — SPEC: ST24P156-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.375		00.06	08.60	T MOD
X	1	025.9	014.3	0.375		00.15	08.60	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-7	.42	.04		

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	K	00019.79	

85421 CONNECTOR RECTANGULAR RACK AND PANEL P/N MM22G5-44SK2H AND P/N MMDIP2265-44SL2L GID: BCXXXX

MANF: DALE MANUFACTURING — SPEC: MIL-C-28748

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.250		0.006	00.25	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61308 CONNECTOR S-L-C28804-100-3N GID: BCXXXX

MANF: HUGHES AIRCRAFT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.40	.05	.35	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	A	00035.92	

62249 CONNECTOR SCOTCHFLEX SOCKET GID: FCXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.250		00.05	02.70	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	A	00004.62	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005525 4

63300 CONNECTOR SEALING PLUG AL/NI GID: BCMAJF
MANF: ITT CANNON SPEC: MIL-C-83723

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	00001.40	

62190 CONNECTOR SILICONE GID: FCXXXX
MANF: MARLIN MFG CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-6	.22	.00		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

61769 CONNECTOR SILICONE/RUBBER 40S GID: BCDPXX
MANF: DEUTSCH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.750		00.17	01.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-7	.32	.05		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

61645 CONNECTOR TAPE RECORDER GID: FCXXXX
MANF: DATEL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	01259.58	

61647 CONNECTOR TAPE RECORDER GID: FCXXXX
MANF: DATEL
MOLEX INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.0E-7	1.62	.02		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	01259.58	

63991 CONNECTOR THERMAL PLASTIC GID: BCXXXX
MANF: AMP INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.03	.00	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	00015.76	

64815 CONNECTOR/CABLE GID: BCBSCA
MANF: HUBBELL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7			00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62025 CONTAINER FOOD NYLON GID: EYBSXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	2.000		00.13	04.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00070.37	

60752 COOLANT FC-40 GID: BWXXXX
MANF: 3M CO

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005526 6

60752 COOLANT FC-40 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	100	0.050	0	20
I	PNEU	1000		70	0.060	0	03
X	PNEU	10000		70	0.060	2	09
B	MECH	150	72	100	0.050	0	20
I	PNEU	2000		70	0.060	0	03
B	PNEU	2500		70	0.060	0	20
B	PNEU	3000		70	0.060	1	20
B	PNEU	3500		70	0.060	0	20
I	PNEU	4000		70	0.060	0	06
I	PNEU	6000		70	0.060	0	08
B	PNEU	8500		70	0.060	0	20

20614 CORD BOOT LACES
MANF: ST LOUIS BRAID CO
....NO TEST DATA AVAILABLE....

62756 CORD BUNGEE 3862T17 GID: EUBSXX
MANF: MCMASTER CARR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5				10.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00103.30	

62486 CORD CELION 6000 EPOXY/CARBON GID: EUFOBG
MANF: HEXCEL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.1E-6	1.34	.18	.58	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

60757 CORD DACRON 1101 P2 GID: EUCBXX
MANF: GUDEBROD BROS SILK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	1.12	.43	.11	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.09	

62153 CORD DACRON 3 GID: EUCBXX
MANF: PREMIER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.05	.04	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

20428 CORD DACRON BRAIDED TROLL 70LB GID: EUCBXX
MANF: CORTLAND LINE
WELLINGTON PURITAN
SPEC: ST14C671-05

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.032		00.17	12.00	T MOD
X	1	025.9	014.3	0.032		00.77	12.00	T MOD
X	2	025.9	014.3			00.14	12.00	T MOD
X	1	025.9	014.3			00.12	12.00	T MOD
X	1	030.0	009.0			00.13	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00020.24	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005527 8

20732 CORD ELASTIC EXERCISER
MANF: SPEC: MIL-C-5651T3
....NO TEST DATA AVAILABLE....

61279 CORD ELASTIC NOMEX COVERED GID: EJBVHD
MANF: WORCESTER BRAIDING

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.095		00.27	12.00	T MOD	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							V	00020.23	

60706 CORD ELASTIC RUBBER/KEVLAR/COTTON GID: EUDHJH
MANF: THOMAS TAYLOR & SONS SPEC: MIL-C-5651CT1

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.300		00.06	06.40	T MOD	No test data		No test data							

60405 CORD FIBERGLASS GID: EUGDXX
....NO TEST DATA AVAILABLE....

05507 CORD FIBERGLASS RESIN TREATED GID: EUFVXX
MANF: OWENS CORNING SPEC: MIL-1-3158TYS

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.024			02.30	NONE	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	4.4E-6	.24	.01			No test data			

06527 CORD FIBERGLASS/NEOPRENE GID: EUFVDB
MANF: JONATHAN TEMPLE INC

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7				00.20	NONE	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.0E-6	5.69	2.93	.00		No test data			

60210 CORD JET HMX AND RL-20-X
MANF: SPEC: MIL-H-45444
....NO TEST DATA AVAILABLE....

61109 CORD KEVLAR GID: BFJHXX
MANF: DUPONT SPEC: EI 4065

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.0E-6	3.94	.52			No test data			

05923 CORD KEVLAR 1600 KDE 29 ARAMID
MANF: DUPONT
....NO TEST DATA AVAILABLE....

65073 CORD KEVLAR 275KOZ3/300 POLYU GID: EUJHCQ
MANF: WESTERN FILAMENT

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
B	1.6E-6	2.24	.06	1.55	48H-257F-	No test data			

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005528 T

61958 CORD KEVLAR 29 73457 GID: EUJHXX
MANF: ASHAWAY LINE & TWINE
SPEC: STSV09-9 STSV091-9

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.032			00.60	NONE
B	1	025.9	014.3	0.032			06.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-7	9.62	2.64		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.01	

TOXICITY

06450 CORD KEVLAR 29 B/B 16X15
MANF: CORTLAND LINE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.73	.14	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

20540 CORD KEVLAR B275 GID: BMJHXX
MANF: DUPONT
SPEC: ST14K963

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.160			01.30	NONE
I	1	033.0	014.3	0.160		00.05	11.70 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.98	.03	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

06511 CORD KEVLAR BB2912 30/12X30 GID: EUXXXX
MANF: CORTLAND LINE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3				00.30	NONE
A	1	030.0	009.0				00.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.20	

TOXICITY

62757 CORD KEVLAR POLYURETHANE COATED GID: EUJHCQ
MANF: WESTERN FILAMENT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.055			02.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05574 CORD KEVLAR/NOMEX GID: EUBVCD
MANF: FABRIC RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.191			00.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00020.01	

TOXICITY

06253 CORD KRT-300 ARAMID GID: EUJHXX
MANF: WESTERN FILAMENT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	009.0	0.045			02.30	NONE
A	1	025.9	014.3	0.045			03.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005529 1

06253 CORD KRT-300 ARAMID (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.045			04.10	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	4.45	.16	2.25	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	K 00020.12	

05630 CORD NOMEX 1200 DENIER GID: EUBVXX

MANF: SYNTHETIC TEXTILE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7				02.30	NONE
A	1	023.8	014.5	0.005			03.60	NONE
I	1	030.0	010.0			02.40	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.4E-6	2.87	.05		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	V 00014.76	

20288 CORD NOMEX 150 LB GID: BFBYXX

MANF: BALLY RIBBON MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.0	010.5	0.084		00.18	12.00 T	NONE
I	1	025.9	014.3	0.084		00.28	12.00 T	NONE
X	1	100.0	016.5	0.084		01.11	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	4.22	.68		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.29	

05629 CORD NOMEX 2400 DENIER GID: EUBVXX

MANF: SYNTHETIC TEXTILE

SPEC: MIL-C-572

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.004			02.90	NONE
I	1	030.0	010.0			00.60	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.4E-6	4.64	.18		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	V 00020.11	

62305 CORD NOMEX BRAIDED GID: EUBVXX

MANF: STAYLASTIC

SPEC: ST14N331-01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.35	

20411 CORD NOMEX/NEOPRENE COATED 1/8 IN GID: BHXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.083		00.19	05.50 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	V 00007.77	

20498 CORD NYLON GID: EUBSXX

MANF: GLADDING CORP

SPEC: ST14N162-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.025		00.21	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005530 8

20498 CORD NYLON (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.025		01.64	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	6.9E-6	16.95	7.34		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00020.25	

64964 CORD NYLON GID: EUBSXX
MANF: CALIFORNIA PLASTECK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.250			00.80	SMALL
A	1	020.9	014.7	0.375			03.50	SMALL
A	1	020.9	014.7	0.500			02.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61616 CORD NYLON BRAIDED 50 GID: EUBVXX
MANF: GLADDING CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3			00.41	12.00	T MOD
X	1	025.9	014.3			00.90	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.87	

60164 CORD NYLON CORELESS GID: EUBSXX
MANF:
SPEC: MIL-C-7515
....NO TEST DATA AVAILABLE....

20513 CORD NYLON G1008 1/8 DIA GID: EUBSXX
MANF: WELLINGTON PURITAN
SPEC: ST14C737-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3				00.50	NONE
X	1	025.9	014.3			00.15	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.2E-7	2.91	.33		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.21	

00299 CORD PARACHUTE NYLON GID: EUBSXX
MANF: A H RICE
....NO TEST DATA AVAILABLE....

60519 CORD PBI STYLE S121 GID: EUHEXX
MANF: FABRIC RESEARCH LAB
SPEC: ST14C953-01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.8E-6	7.95	.00		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

60659 CORD POLYESTER
MANF: WELLINGTON PURITAN
....NO TEST DATA AVAILABLE....

61362 CORD POLYESTER .0625 NATURAL GID: COCBXX
MANF: BALLY RIBBON MILLS
SPEC: ST14P134-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005531 T

61362 CORD POLYESTER .0625 NATURAL (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.2E-6	2.33	.33		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

80003 CORD POLYESTER 80 GID: EUCBXX

MANF: GLADDING CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3				00.80	NONE
X	1	025.9	014.3			00.50	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00019.83	

60408 CORD SF2600 GID: EUXXXX

....NO TEST DATA AVAILABLE....

03449 CORD SF429 GLASS/TFE COATED GID: EUCNIA

MANF: SANTA FE TEXTILES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.058			00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.1E-5	.42	.14		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.14	

80071 CORD SHOCK RUBBER COVERED NYLON (BUNGEE)

MANF: HECT RUBBER CORPORATION

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	010.0		00.20	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

20373 CORD SHOCK RUBBER/KEVLAR/COTTON GID: EUJHFS

MANF: SPAR AEROSPACE SPEC: MIL-C-5651CT1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.301		00.08	12.60	T MOD
A	1	025.9	014.3	0.597		00.00	00.00	NONE
X	1	033.0	014.3	0.520		00.03	12.70	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	V 00045.67	

65166 CORD SILVERTON 55-1 ORANGE GID: EUCBDU

MANF: TUBBS CORDAGE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.380		00.10	12.00	T NONE
X	1	020.9	014.7	0.380		00.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

62298 CORD YALE 375 QUAD DACRON/KEV GID: EUCBXX

MANF: YALE CORDAGE INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	19.92	11.49	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005532 1

06534 CORE ARAMID PHENOLIC COATED GLASS FILLED SPEC: MB0130-174

MANF:

....NO TEST DATA AVAILABLE....

62732 CORE ASSEMBLY 7U82634 GID: EXXXXX

MANF: MORTON THIOKOL

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7			00.01	26.00	T MOD	No test data		No test data							

05615 CORE HONEYCOMB PHENOLIC/GLASS GID: EXIAXX

....NO TEST DATA AVAILABLE....

05007 CORE HONEYCOMB/ALUMINUM FACE PLATES ADHESIVE BONDED GID: BBBGIA

MANF: HEXCEL SPEC: MIL-C-7438

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.500			02.10	SMALL	No test data		No test data							
A	1	030.0	009.0	0.500			05.50	SMALL										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.68	.10		

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	A	00025.27	

05325 CORE HRH-10 NOMEX/PHENOLIC GID: BBBVBX

MANF: HEXCEL SPEC: MB0135-135

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.253			03.60	NONE	No test data		No test data							
A	1	023.8	014.5	0.250			04.40	NONE										
A	1	025.9	014.3	0.380			03.30	NONE										
I	1	033.0	014.3	0.380		00.36	11.80	T NONE										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	6.2E-7	2.15	.00		16H-250F-

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	X	00002.47	

05006 CORE HRP/HFT GLASS/PHENOLIC HC GID: COBXIA

MANF: HEXCEL SPEC: MB0130-014 MB0130-148

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.400			01.90	NONE	No test data		No test data							
A	1	030.0	009.0	0.600			01.00	NONE										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.30	.20	.00	

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	V	00019.65	

05749 CORE SPIRALGRIP/A1GG220 FM1000

....NO TEST DATA AVAILABLE....

60071 CORK AB 600

....NO TEST DATA AVAILABLE....

60250 CORK B STAGE SPEC: USB-MS-1005

MANF:

....NO TEST DATA AVAILABLE....

60716 CORK B-380FA GID: BBFRXX

MANF: DODGE CORK CO INC

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005533 3

60716 CORK B-380FA (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.121		00.30	11.50 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00017.95	

62758 CORK B-STAGED/COATING TURCO T6109 GID: AKFRXX

MANF: TURCO PROD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.250	0.125	00.04	12.0 T	NONE
A	1	020.9	014.7	0.500			03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60226 CORK COMPOSITION SPEC: USB-MS-1001

MANF:

....NO TEST DATA AVAILABLE.....

60219 CORK COMPOUND K5NA SPEC: USB-MS-2004

MANF: ARMSTRONG CORK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7		0.003		03.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62759 CORK P50/ADHESIVE RTV 560 GID: ABFRXX

MANF: SHELLER GLOBE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.500			04.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62761 CORK P50/COATING 051-A69 GID: AKFRXX

MANF: SMITH ALSOP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.500	0.125	00.13	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62760 CORK P50/COATING FRL-3 GID: ABFRXX

MANF: MARTIN MARIETTA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.500			01.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62762 CORK P50/COATING TURCO T6109 GID: AKFRXX

MANF: PUREX CORP
TURCO PROD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.500	0.125	00.02	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62763 CORK/HYPALON HFR2200

MANF: GACO WESTERN INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.500			02.70	NONE
X	1	020.9	014.7	0.030		00.24	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0005534 5

Information Handling Services, 2000

62764 CORK/HYPALON HFR2200/ACTIVATOR GID: AKXXXX
MANF: GACO WESTERN INC

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.500	0.125		02.80	SMALL	No test data		No test data							

63885 COVER DUST FES BETA/VELCRO GID: BFXXXX
MANF: NASA/MSFC
VELCRO CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	00029.30	

20684 COVER EYE CELEBRITY SLEEP REST
....NO TEST DATA AVAILABLE....

20604 CREAM HAND/KERI GID: DDXXXX
MANF: WESTWOOD

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	00080.57	

20598 CREAM SHAVE BRUSHLESS GID: DDXXXX
MANF: COLGATE-PALMOLIVE

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	00145.68	

20544 CREME NIVEA SKIN CARE GID: DJXXXX
MANF: BEIERSDORF INC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	X 00019.80	

20599 CREME SHAVE BRUSHLESS
MANF: GILLETTE
....NO TEST DATA AVAILABLE....

65543 CU CLAD FR4/PCB WITH MS-470 COATING GID: EXXXXX
MANF: MILLER STEPHENSON SPEC: MIL-P-13949

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	024.5	014.3	0.005			01.75	NONE	No test data		No test data							

20687 CUFFS ROLL-ON GID: DDACXX
MANF: GSA

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	00020.98	

61292 CURTAIN HYGIENE CLOSURE GID: BFCBXX
MANF: ROCKWELL SPEC: MIL-C-38351T2C1 MIL-T-4363C

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.040		00.00	00.00	NONE	No test data		No test data							
A	1	030.0	009.0	0.040		00.00	00.00	NONE										

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005535 7

06387 CUSHION SEAT CREW WITH PASSENGER GID: BFBYCQ
MANF: AMI INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	1.600			03.00	NONE
A	1	030.0	009.0	1.600			00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00110.34	

05442 CYCOLOY KHS GID: DKAIXX
MANF: BORG WARNER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.150			00.70	NONE
A	1	030.0	008.0	0.150		00.03	12.00	T SMALL
X	1	040.0	008.0	0.150		00.02	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.6E-6	.30	.00		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.08	

62787 DAMPER VIBRATION VHDS 33 DIDC
MANF: VIBRA-CHECK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.150		00.25	02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00137.52	

63193 DAP VINYL/GRAPHITE GID: DTCUGF
MANF: ALLFORCE ACOUSTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.031		00.50	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64217 DEBRIS FROM ISS-DEBRIS TRAP
....NO TEST DATA AVAILABLE....

62419 DECAL FOTOFOIL P GID: CNXXXX
MANF: MILLER DIAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.004			02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00022.85	

80029 DECALS AF-1-33/TAPE B-184 GID: CNXXXX
MANF: W H BRADY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.0E-6	.94	.24	.07	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

63963 DELECTED SKE 20877

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	020.9		014.7		00.10

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005536 9

00140 DELRIN 500 GID: DLAJXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.150		00.09	12.00	T MOD
X	1	030.0	010.0	0.150		00.09	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE
A	00010.01	

65155 DELRIN ACETAL
MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.24	.02	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

62189 DENTURE ACRYLIC ACRA-WELD T2C1 GID: FCAKXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.500		00.47	01.90	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00009.57	

20608 DEODORANT BRITISH STERLG SOLID GID: DDXXXX
MANF: SPEIDEL/TEXTRON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00134.82	

20605 DEODORANT DIAL SOLID
MANF: DIAL INDUSTRIES
....NO TEST DATA AVAILABLE....

20607 DEODORANT ENGLISH LEATHR SOLID GID: DDXXXX
MANF: ENGLISH LEATHER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00137.98	

20672 DEODORANT MITCHUM STICK GID: DDXXXX
MANF: REVLON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00120.68	

20606 DEODORANT OLD SPICE SOLID GID: DDXXXX
MANF: SHULTON INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00118.00	

20545 DEODORANT SOLID ANTI-PERSPIRNT GID: DJXXXX
MANF: BRISTOL MYERS CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00099.12	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005537 0

20543 DEODORANT SOLID UNSCENTED GID: DJXXXX
MANF: ALMAY INC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							X	00070.91	

64321 DEODORANT SPEED STICK GID: EXXXXX
MANF: MENNEN CO

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							X	00079.74	

05115 DESICCANT MOLECUL SIEVE INORG GID: EXXXXX
....NO TEST DATA AVAILABLE....

61938 DESICCANT NBR48213 GID: AAXXXX
MANF: 3M CO

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	A 00021.42	

20818 DESICCANT SILICA GELL
MANF: SPEC: MIL-D-3716T4GRH
....NO TEST DATA AVAILABLE....

61709 DESTRUX QC SEAL GID: CNXXXX
MANF: AVERY INTERNATIONAL

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	3.5E-6	4.16	.83				A	X 00006.63	

66264 DEVCON SUPER LOCK-SCREW LOCKING GRADE 18510
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

62901 DEVELOPER D-1
MANF: OXY METAL INDUSTRIES

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	14.7	72	-297		0	20

62882 DEVELOPER D90
MANF: SHERWIN INC SPEC: MMS-Y-846

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	14.7	72	-297		0	20

62900 DEVELOPER NQ-1
MANF: OXY METAL INDUSTRIES

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	14.7	72	-297		0	20

64196 DIAPHRAGM SILICONE/NOMEX GID: CHDPBY
MANF: DIAPHRAGM INDUSTRIES

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	020.9	014.7	0.030		00.10	14.00	T NONE	No test data		No test data						

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005538 2

64196 DIAPHRAGM SILICONE/NOMEX (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.8E-6	1.27	.35	.26	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

65170 DISC AL LITHIUM ALLOY GID: FIMAXX

MANF: ROCKWELL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	275	72	-297	0.110	0	20

20694 DISH SOAP HSB 2

MANF: SIRLSA PRODUCTS

....NO TEST DATA AVAILABLE....

66387 DOLCHEM 6009

MANF: DOLPHIN PAINT & CHEMICAL

....NO TEST DATA AVAILABLE....

66375 DOLPHON CB-1109

MANF: JOHN C DOLPH CO

....NO TEST DATA AVAILABLE....

63318 DREWGARD 100 GID: DDXXXX

MANF: DREW CHEMICAL CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297		0	20
B	MECH	14.7	72	-297		00	420

63319 DREWGARD 187 GID: DDXXXX

MANF: DREW CHEMICAL CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297		0	20

60724 DRIVER IMPACT PIT-120 GID: FCXXXX

MANF: SNAP-ON-TOOLS

SPEC: ST20T1013-65

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	00635.36	

62212 DUCT E-720-E FR/120/MBO125-070 GID: COBGIA

MANF: U S POLYMERIC

SPEC: MBO130-127T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.035		00.09	17.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	0.8E-6	1.53	.06		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05724 DUCT GLASS/POLYIMIDE 7781/F178 GID: COCDIA

MANF: HEXCEL

SPEC: MBO130-0104T8 MBO130-104T8B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.018			02.30	NONE
C	2	023.8	014.5	0.027			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005539 4

05724 DUCT GLASS/POLYIMIDE 7781/F178 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	023.8	014.5	0.027		00.21	12.00	T NONE
I	1	025.9	014.3	0.018		00.36	12.00	T SMALL
A	1	033.2	015.5	0.018			04.70	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

62380 DUCT NEOPRENE IMPREG CTN FAB GID: EGFDFS

MANF: CALLAHAN MINING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.130			00.30	NONE
A	1	030.0	010.4	0.130			00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00106.90	

62416 DUCT RUBBER GID: DOXXXX

MANF: ARROWHEAD PRODUCTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00117.77	

62791 DUCT SILICONE IMPREG 5276K22 GID: EFDPXX

MANF: MCMASTER CARR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.2			00.25	04.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06252 DUCT SILICONE/HT6 NOMEX

MANF: AQM

SPEC: MIL-W-38283 T1

....NO TEST DATA AVAILABLE....

61217 DUCT VENT ASSEMBLY GID: FGXXXX

MANF: DAVID CLARK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00470.42	

62299 DUCTING RUBBER IMPREG COTTON GID: EXHDFS

MANF: SMALLCOMB ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.046		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65310 DURA-TUFF #4776

MANF: DURACOTE CORPORATION

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00022.58	

05486 DYE GREEN

....NO TEST DATA AVAILABLE....

20065 DYE RED GID: DDXXXX

MANF: AQM

SPEC: MIL-C-554

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005540 0

65678 DYMAX 840 OIL/GRIP
MANF: AMERICAN CHEMICAL
....NO TEST DATA AVAILABLE....

61140 EARPHONE HD-424 GID: FCXXXX
MANF: SENNHEISER ELECTRONICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00021.39	

20685 EARPLUGS 4560 GID: FGXXXX
MANF: MOBILE INDUSTRY SAFE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00059.74	

60935 EARSEAL 61B883 URETHANE/FLOURL GID: FCCQDE
MANF: GENTEX CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.732		00.18	04.50	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20643 ECCOGEL 1265/CABOSIL
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

20645 ECCOGEL 1265/EPOXY GID: BABVXX
MANF: EMERSON AND CUMING SPEC: SV8507 TYC SVHS 8507TB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.600		00.00	00.00	NONE
A	1	025.9	014.3	0.500		00.00	00.00	NONE
X	2	025.9	014.3	0.092			07.00	MOD
X	1	025.9	014.3	0.092		00.15	12.00	T MOD
X	2	100.0	019.0	0.500			04.20	MOD
X	1	100.0	019.0	0.500		00.07	12.00	T NONE
X	2	100.0	019.0	0.600			07.40	MOD
X	1	100.0	019.0	0.600		00.08	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	16.59	8.66	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.29	168H-70F-

65309 ELASTOMER PMF GID: DCXXXX
MANF: ADVANCE SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297		1	01

63388 ELECTRICAL ASSEMBLY GID: EZXXXX
MANF: MARTIN MARIETTA

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	100.0	042.0			00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61272 ELECTRICAL CONNECTOR WITH FIBERITE FM4051 GID: BCXXXX
MANF: FIBERITE SPEC: 40M39569

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00081.70	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005541 2

61273 ELECTRICAL CONNECTOR WITH MOLD COMPOUND RX660 GID: AZXXXX
MANF: ROGERS CORP SPEC: 40M37569 40M38298

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.73	.01	.56	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00080.90	

20278 ELECTROLYTE KOH 6N (INORGANIC)
....NO TEST DATA AVAILABLE....

20414 EMBLEM CLOTH NASA GID: BFXXXX
MANF: LION BROTHERS CO SPEC: ST10L719-01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	9.38	3.59	.00	

ODOR

RT
No test data

TOXICITY

60762 EMBLEM CLOTH SHUTTLE GID: CNXXXX
MANF: CONRAD INDUSTRIES SPEC: ST10P1165-01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.22	.07	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00005.91	

20415 EMBLEM CLOTH US FLAG GID: BFXXXX
MANF: HARRY SUGARMAN INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.20	.03	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00023.22	

60621 ENVEX 100 POLYIMIDE GID: DKCDXX
MANF: ROGERS CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.4E-6	2.20	.00	1.17	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00086.41	

61069 ENVEX 1000 POLYIMIDE GID: DKCDXX
MANF: ROGERS CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRE	IMPACT	TEMP	THICK	#REACT	#TEST
I	PNEU	100u		70	0.070	0	02
X	MECH	1000	15	70	0.070	0	20
B	PNEU	2000		70	0.070	0	20
X	PNEU	2500		70	0.070	2	03
X	PNEU	3000		70	0.070	1	01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.94	.01		

ODOR

RT
No test data

TOXICITY

61021 ENVEX 1115 POLYIMIDE GID: DKCDXX
MANF: ROGERS CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.67	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.74	

61071 ENVEX 1228 POLYIMIDE/PTFE GID: DKCDCP
MANF: ROGERS CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	70	0.060	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005542 4

61071 ENVEX 1228 POLYIMIDE/PTFE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	PNEU	1000		70	0.061	0	02
B	MECH	2000	72	70	0.060	0	20
I	PNEU	2000		70	0.060	0	02
B	PNEU	3000		70	0.060	0	20
Z	MECH	3000	72	70	0.060	2	09
X	PNEU	3500		70	0.060	2	13
X	PNEU	3500		70	0.061	2	13
X	PNEU	4000		70	0.060	1	09
X	PNEU	5000		70	0.060	1	15
X	PNEU	6000		70	0.060	1	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.29	.00	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE

No test data

61070 ENVEX 1330 POLYIMIDE/GRAPHITE GID: DKCDGF

MANF: ROGERS CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	1000	40	70	0.059	0	20
I	PNEU	1000		70	0.061	0	02
I	PNEU	2000		70	0.061	0	02
I	PNEU	3000		70	0.061	0	02
I	PNEU	4000		70	0.061	0	02
I	MECH	500	72	70	0.059	0	12
I	PNEU	5000		70	0.061	0	02
B	PNEU	6000		70	0.061	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.9E-6	1.12	.00		44H-70F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE

No test data

20464 ERASER RUBBER PINK PEARL GID: DOHDXX

MANF: EBERHARD FABER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.430		00.30	01.90	T NONE

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
V	00011.55	

69994 ETCHANT

MANF: W L GORE

....NO TEST DATA AVAILABLE....

60387 ETCHANT-BONDAIV S16943

MANF: YYB SHAMB & CO

SPEC: USBI99611-0000

....NO TEST DATA AVAILABLE....

60201 EXPLOSIVE HNS TYPE 1 GRADE A

....NO TEST DATA AVAILABLE....

60208 EXPLOSIVE PETN

MANF:

SPEC: MIL-P-387

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005543 6

60184 EXPLOSIVE RDX/LSC
MANF:
SPEC: STW3-2808
....NO TEST DATA AVAILABLE....

60743 EYE COLOR FROST FORMULA 2 GID: DDXXXX
MANF: REVLON

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data							V 00016.95	

60909 EYE COLOR STICK PROFESSIONAL GID: DDXXXX
MANF: REVLON

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data							X 00007.09	

20627 EYE LINER GID: EXXXXX
MANF: REVLON

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data							V 00020.04	

20625 EYE MAKEUP REMOVER 30 SEC GID: EXXXXX
MANF: REVLON

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data							A 00084.85	

60741 EYE PENCIL ALMAY COLOR GENTLE GID: DDXXXX
MANF: ALMAY INC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data							A 00005.62	

60901 EYE SHADOW #35-4.023-4091 GID: DDXXXX
MANF: VIVIAN WOODWARD

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data							A 00005.91	

20657 EYE SHADOW BLUEBERRY GID: DDXXXX
....NO TEST DATA AVAILABLE....

20626 EYE SHADOW CREAM-ON SUPER LUST GID: EXXXXX
MANF: REVLON

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data							X 00021.70	

20698 EYE SHADOW CREME SKYLIGHT BLUE GID: DDXXXX
MANF: ESTEE LAUDER

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data							X 00024.04	

20697 EYE SHADOW CREME-SIL FROSTBLUE GID: DDXXXX
MANF: MAYBELLINE CO

MSFC-HDBK-527 REV F 9999942 0005544 8

Information Handling Services, 2000

20697 EYE SHADOW CREME-SIL FROSTBLUE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00017.11	

20699 EYE SHADOW LT BLUE GID: DDXXXX

MANF: MERLE NORMAN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00016.14	

60900 EYE SHADOW PENCIL MAXI-SOFT GID: DDXXXX

MANF: MAX FACTOR

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00005.99	

62156 FABRIC 100% COTTON FR 7 OZ BLUE GID: BFFSXX SPEC: ST11C709-01 ST11C709-03

MANF: COTTON INC
REEVES BROS
WESTERN PIECE DYERS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.034		108	12.20	T NONE
I	1	025.9	014.3	0.020		065	12.00	T NONE
B	1	025.9	014.3	0.016		108	08.20	NONE
B	1	025.9	014.3	0.050			08.50	NONE
A	1	025.9	014.3	0.019			05.80	NONE
I	1	033.0	014.3	0.019		01.58	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.05	

65131 FABRIC 100% COTTON KNIT JERSEY GID: BFFSXX

MANF: FLEXITHERM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.020		00.20	01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.13	

69909 FABRIC 1213 TY1 CL1 NEOPRENE-COATED NYLON

MANF: CHEMTEK INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.010			00.40	NONE
C	1	025.9	014.3	0.010		0.80	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	10.451	

62924 FABRIC 46% COTTON/POLYESTER/LYCRA GID: BFFSCB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	024.5	014.3	0.017		00.12	12.00	T NONE
C	1	024.5	014.3	0.017		01.26	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005545 T

06153 FABRIC 5035/8362 BETA/SILICONE GID: BFHLCK

MANF: J P STEVENS

....NO TEST DATA AVAILABLE....

62354 FABRIC 520/S920 SILANE FINISH GID: BFXXXX

MANF: CAROLINA FABRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.2E-6	.03	.00	.01	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20346 FABRIC 6007-1-1-54 HEAVY WT GID: BFXXXX

MANF: UNIROYAL SPEC: ST11T614-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.281			00.30	NONE
B	1	025.9	014.3	0.281			10.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.2E-7	5.66	1.64		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.66	

TOXICITY

20911 FABRIC 6009-1-1 GID: BFXXXX

MANF: LAUREL INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.090			00.40	NONE
C	1	025.9	014.3	0.090		00.20	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	K 00022.44	

TOXICITY

63735 FABRIC 65 POLYESTER/35 COTTON GID: BFFSCB

MANF: SPRING MILLS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	1.44	.09	.92	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06380 FABRIC 7878 FIRE/WATER PROOF GID: BFFSXX

MANF: ROCKWELL SPEC: MA0105-330

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.016		00.00	00.00	NONE
A	1	030.0	009.0	0.016			01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00019.99	

TOXICITY

69905 FABRIC 800116-1 NEOPRENE-COATED NYLON GID: BFXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.010		0.10	07.50	NONE
C	1	025.9	014.3	0.010		1.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	A 21.355	

TOXICITY

20330 FABRIC AB06-80MEL MULTI-FIL GID: BFXXXX

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005546 1

64035 FABRIC AIRC-S236 GID: BFCBXX
MANF: ALBANY INTERNATIONAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.007		00.40	12.00	T MOD
X	1	030.0	010.0	0.007		00.70	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00008.40	

61281 FABRIC AIRC73300-233 GID: BFFSXX
MANF: CELANESE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.023			01.10	NONE
A	1	030.0	009.0	0.023			01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05391 FABRIC AL GLASS/SILICONE SRGA/0409V RD GID: BFIACK
....NO TEST DATA AVAILABLE....

80026 FABRIC ALUMINIZED DS662 POLYURETHANE POLYESTER COATED GID: BFFJCB
MANF: REEVES BROS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.012		0.4	02.60	NONE
B	1	025.9	014.3	0.012		0.4	07.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	21.526	

65193 FABRIC ALUMINIZED M11678 NEOPRENE KEVLAR COATED WITH POLYURETHANE OC GID: BFCQXX
MANF: AIR CRUISERS CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.020			04.00	SMALL
B	2	025.9	014.3	0.010			00.10	NONE
B	1	025.9	014.3	0.010		01.30	09.50	NONE
C	1	030.0	010.0	0.010		01.20	12.00	T NONE
C	2	030.0	010.0	0.012			00.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	21.339	

80053 FABRIC ALUMINIZED M11849-5 POLYURETHANE COATED GID: BFFJBS
MANF: URETEK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.010		0.1	12.00	T MOD
X	1	025.9	014.3	0.010		0.5	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	9.739	

80024 FABRIC ALUMINIZED MS452 POLYURETHANE COATED NYLON GID: BFFJBS
MANF: URETEK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.010		0.1	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005547 3

80024 FABRIC ALUMINIZED MS452 POLYURETHANE COATED NYLON (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.010		0.5	12.00 T	MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	22.819	

80023 FABRIC ALUMINIZED MS458 POLYURETHANE COATED NYLON GID: BFFJRS

MANF: REEVES BROS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.015		00.09	12.00 T	SMALL
X	1	025.9	014.3	0.015		0.6	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	9.309	

69923 FABRIC ALUMINUM M11481

MANF: URETEK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.014		00.09	12.00 T	NONE
X	1	025.9	014.3	0.014		00.70	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	22.027	

60481 FABRIC ANCHORAGE 2 GID: BFBVXX

MANF: COLLINS & AIKMAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.053			09.60	NONE
B	1	025.9	014.3	0.050			09.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00045.37	

61054 FABRIC ANCHORAGE 2 BLUE 69/1211 GID: BFBVXX

MANF: COLLINS & AIKMAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.030			00.10	NONE
A	1	023.8	014.5	0.030			04.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.8E-6	8.05	1.92		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00026.08	

61857 FABRIC ARAMID 3/K-GUARD 787818 GID: BFBVXX

MANF: KLOPMAN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.016			00.40	NONE
C	1	023.8	014.5	0.016		00.20	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00013.17	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005548 5

62943 FABRIC ARGMAMITE GRAPHITE COATED GID: BFGFCQ

MANF: 3M CO
HERCULES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.026			00.50	NONE
B	1	020.9	014.7	0.026		00.27	07.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61327 FABRIC AROMATIC POLYAMIDE GID: BFCDXX

MANF: GIBRALTER INDUSTRIES SPEC: MIL-L-83429T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.012			06.90	NONE
C	1	025.9	014.3	0.012		00.75	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.2E-6	2.68	.16	2.33	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00019.45	

61531 FABRIC AROMATIC/NON-MELTING GID: BFBVXX

MANF: STERN & STERN SPEC: MIL-C-38351T2C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.013			00.20	NONE
X	1	023.8	014.5	0.013		00.33	12.00 T	MOD
X	1	025.9	014.3	0.013		00.25	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.1E-6	3.53	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00012.14	

62792 FABRIC BALLISTIC NYLON/VITON GID: BGBSXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.040		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80248 FABRIC BASE-TREATED COTTON AMMONIA CURE WITH NASA TOPPING (DRY-CLEANED) GID: BFXXXX

MANF: COTTON INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.015			04.60	NONE
A	1	030.0	010.0	0.020			04.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80249 FABRIC BASE-TREATED COTTON AMMONIA CURE WITH NASA TOPPING (WASHED/DRIED 25 TIMES) GID: BFXXXX

MANF: COTTON INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.022		0.9	07.60	NONE
I	1	030.0	010.0	0.022		1.0	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63475 FABRIC BETA CLOTH/PLASTIC COATED GID: BGXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.025		00.20	13.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63387 FABRIC BETA CLOTH/TFE GLASS TAPE GID: BFXXXX

MANF: TACONIC PLASTIC LTD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.012			09.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005549 7

05083 FABRIC BETA GLASS STYLE 81677 GID: BFGDXX

....NO TEST DATA AVAILABLE....

62793 FABRIC BETA GLASS/TFE NOC GID: BFFVCN

MANF: MCDONNELL DOUGLAS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.005		00.00	00.00	NONE
A	1	030.0	009.0	0.005			00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00094.95	

06222 FABRIC BETA SUPER 4484/TFE COATED GID: BFCNXX

....NO TEST DATA AVAILABLE....

03285 FABRIC BETA YARN/TFE GID: BFCNXX

....NO TEST DATA AVAILABLE....

62794 FABRIC BETA/REFSET COATED GID: BGXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	100.0	044.0			00.50	04.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20561 FABRIC BETA/SILICONE 10535/9362 GID: BFCKXX

....NO TEST DATA AVAILABLE....

20360 FABRIC BETA/SILICONE 5035 GID: BFCKXX

....NO TEST DATA AVAILABLE....

61634 FABRIC BETA/SILICONE S85035 GID: BFHLCK

MANF: J P STEVENS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.008			00.40	NONE
A	1	033.0	014.3	0.008			00.60	NONE
A	1	100.0	016.5	0.008		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.02	.00		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00013.37	

03022 FABRIC BETA/TFE COATED 95-049 GID: BFCNXX

MANF: DUPONT

....NO TEST DATA AVAILABLE....

20380 FABRIC BIAS PLY COATED GID: BGCBXX

MANF: REEVES BROS SPEC: ST12P579-1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.014		00.02	08.70	SMALL
C	1	023.8	014.5	0.014		00.87	12.00	T NONE
C	2	025.9	014.3	0.015		00.04	12.00	T SMALL
C	1	025.9	014.3	0.015		01.04	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.0E-7	1.63	.29		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00021.83	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005550 3

63476 FABRIC BUNTING PANTS 31801 GID: BFXXXX

MANF: PATAGONIA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.023		00.12	12.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62795 FABRIC CARBON PHENOLIC ABLATIVE GID: BFBXFO

MANF: FIBERITE

SPEC: MX4926 STW5-2649

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.370		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61291 FABRIC CERAMIC AB312 SILICONE COATED GID: BFHOCK

MANF: 3M CO
ROCKWELL
SWS SILICONES

SPEC: MA0105-331 MB0130-175
MB0135-066

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.020			00.10	NONE
X	1	020.9	014.7	0.020		00.08	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.79	.17	.25	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62444 FABRIC CERAMIC AB312 WITH Z6070 GID: BFHOXX

MANF: 3M CO

SPEC: MB0135-065T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.040		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.9E-6	.10	.05	.01	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62200 FABRIC CERAMIC FELT GID: BIHOXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.9E-6	.15	.00		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65415 FABRIC CHEMSTAT 919 NOMEX GID: BFBVXX

MANF: STERN & STERN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	2.67	.03	2.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60629 FABRIC COTTON 100% COMFORT 3640 GID: BFFSXX

MANF: ALPHA MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	020.2	0.012		15.00	12.00	T NONE
X	1	100.0	020.2	0.012		14.90	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	3.29	.08	2.71	

ODOR

RT	RT WEIGHT	CURE
A	A 00019.84	

TOXICITY

60945 FABRIC COTTON 100%(FR/2%THPOH) GID: BFFSXX

MANF: COTTON INC
REEVES BROS

SPEC: ST11C709 ST11C709-02

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005551 5

60945 FABRIC COTTON 100%(FR/2%THPOH) (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.031			04.90	NONE
I	1	025.9	014.3	0.019		00.91	11.90	T NONE
I	1	030.0	009.0	0.019		01.02	11.90	T NONE
B	1	033.0	014.3	0.031			06.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.00	

61960 FABRIC COTTON 2701 FR GID: BFFSXX

MANF: J P STEVENS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.019			03.90	NONE
A	1	033.0	014.3	0.019			04.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00018.98	

60788 FABRIC COTTON 591 FLOCK GID: FJFSXX

MANF: CLAREMONT FLOCK CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	2.35	.35		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.88	

62216 FABRIC COTTON 7 OZ/LINING 4 OZ FR GID: BFFSXX

MANF: A E NATHAN SPEC: ST11C709-02 ST11C834-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.029			03.00	NONE
A	1	025.9	014.3	0.036			03.20	NONE
A	1	033.0	014.3	0.029			02.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	K 00032.35	

65496 FABRIC COTTON AIRC84410-502/FR GID: BFFSXX

MANF: ALBANY INTERNATIONAL
COTTON INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.110			01.40	NONE
B	1	030.0	010.0	0.010		02.80	10.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63513 FABRIC COTTON BLUE MOUNTAIN GID: BFFSXX

MANF: COTTON INC SPEC: MC-5X MC430-84

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.016		01.05	05.77	SMALL
A	1	030.0	010.0	0.015		00.77	05.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005552 7

60607 FABRIC COTTON CHEESE CLOTH GID: BLFSXX

MANF: NA-TEX CORP SPEC: ST11C1325

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.037		02.54	12.40	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	9.0E-6	4.39	.09		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00020.46	

80245 FABRIC COTTON COVERALL (DRY-CLEANED 25 TIMES) GID: BFXXXX

MANF: ILC DOVER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.4	014.3	0.017		01.20	09.30	NONE
A	1	025.9	014.3	0.015			04.90	NONE
B	1	030.0	010.0	0.035		00.50	20.60	NONE
I	1	030.0	010.0	0.017		01.20	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80246 FABRIC COTTON COVERALL (WASHED/DRIED 25 TIMES)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.017		00.60	17.60	NONE
I	1	025.9	014.3	0.024		01.30	12.00	T NONE
I	1	030.0	010.0	0.033		00.80	19.20	T NONE
I	1	030.0	010.0	0.024		01.20	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62207 FABRIC COTTON DUCKWEAVE FR GID: BKFSXX

MANF: COTTON INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.018		00.86	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
X

TOXICITY

RT	RT WEIGHT	CURE
V	00021.48	

20516 FABRIC COTTON FLAME RETARD 4 OZ GID: BFFSXX

MANF: COTTON INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.022		00.80	11.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00020.03	

20407 FABRIC COTTON FLAME RETARDANT GID: BFFSXX

MANF: COTTON INC SPEC: ST11C709-01
J P STEVENS
REEVES BROS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.019			04.40	NONE
A	1	025.9	014.3	0.014			05.70	NONE
B	1	025.9	014.3	0.016			06.20	NONE
A	1	030.0	009.0	0.019			04.20	NONE
A	1	033.0	014.3	0.019			05.50	NONE
B	2	033.0	014.3	0.014			00.30	NONE
B	1	033.0	014.3	0.014			06.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005553 9

20407 FABRIC COTTON FLAME RETARDANT (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.07	.14		

ODOR

RT	RT WEIGHT	CURE
A	V 00019.96	

TOXICITY

62021 FABRIC COTTON FR/POLYETHYLENE LINING GID: BFFSCF

MANF: J P STEVENS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	4.000			04.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06521 FABRIC COTTON FR7A FIRE STOP GID: BFFSXX

MANF: WESTEX INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.024			00.30	NONE
X	1	025.9	014.3	0.024		01.23	12.00.	T MOD

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	5.44	.13	4.78	

ODOR

RT	RT WEIGHT	CURE
A	A 00020.11	

TOXICITY

20525 FABRIC COTTON HANDKERCHIEF GID: BFFSXX

MANF: R W ELDRIDGE CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.007		02.29	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	A 00010.36	

TOXICITY

20413 FABRIC COTTON INTERFACING GID: BFFSXX

MANF: STACY FABRICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.037		00.67	09.90	T MOD

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	K 00052.90	

TOXICITY

61256 FABRIC COTTON NATURAL GID: BFFSXX

MANF: FLIGHTEX FABRIC CO SPEC: MIL-C-5646T1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.35	.12		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20526 FABRIC COTTON POCKET CWG GID: BFFSCB

MANF: ILC DOVER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.174			03.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	A 00008.93	

TOXICITY

62042 FABRIC COTTON RED GID: BFFSXX

MANF: COTTON INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.013		01.97	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005554 0

62042 FABRIC COTTON RED (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00016.73	

62360 FABRIC COTTON S55 F/P/VELCRO/NOMEX GID: BFFSCB

MANF: VELCRO CORP
WESTEX INC

SPEC: MIL-T-43636T2E

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.181		00.11	12.10	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06548 FABRIC COTTON S55 F/PNH3 D/F GID: BFFSXX

MANF: COTTON INC
WESTEX INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.013			04.00	NONE
A	1	030.0	009.0	0.013			03.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.16	

06549 FABRIC COTTON S65 F/PNH3 D/F GID: BFFSXX

MANF: COTTON INC
WESTEX INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.020			03.60	NONE
A	1	030.0	009.0	0.021			04.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.91	

61950 FABRIC COTTON SHAPE-FLEX LINING GID: BFFSXX

MANF: STACY FABRICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.014		01.48	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00007.55	

61948 FABRIC COTTON SHIRTING MC PP1 GID: BFFSXX

MANF: COTTON INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.017			04.90	NONE
I	1	025.9	014.3	0.015		00.98	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	3.95	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00014.41	

61946. FABRIC COTTON SHIRTING/TOPSOFT GID: BFFSXX

MANF: COTTON INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.016			05.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

80027 FABRIC COTTON SLEEP RESTRAINT GID: BFFSXX
MANF: COTTON INC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	030.0	010.0	0.017			04.50	NONE	No test data	No test data							
I	1	032.0	010.0	0.015		1.3	12.20	T NONE									

20302 FABRIC COTTON STYLE 3715 COMBD GID: BFXXXX
MANF: MAY HOSIERY MILLS
....NO TEST DATA AVAILABLE....

63477 FABRIC COTTON TWILL GID: BFFSXX
MANF: COTTON INC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	030.0	010.0	0.012		00.31	05.00	NONE	No test data	No test data							

80091 FABRIC COTTON TWILL GRT8134 GID: BFFSXX
MANF: COTTON INC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.017			03.50	NONE	No test data	No test data							
B	1	030.0	010.0	0.092		00.60	09.70	NONE									
A	1	030.0	010.0	0.017			03.80	NONE									

61949 FABRIC COTTON TWILL SHIRTING GID: BFFSXX
MANF: COTTON INC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	023.8	014.5	0.017			09.50	NONE	No test data	No test data							

61947 FABRIC COTTON WESTEX SATINE GID: BFFSXX
MANF: COTTON INC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	023.8	014.5	0.025			11.50	NONE	No test data	No test data							

61945 FABRIC COTTON WESTEX TWILL GID: BFFSXX
MANF: COTTON INC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	023.8	014.5	0.025			06.30	NONE	No test data	No test data							

62155 FABRIC COTTON/DACRON GID: BFFSCB
MANF: KLOPMAN MILLS SPEC: ST11D126-01

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	025.9	014.3	0.010		01.51	12.00	T NONE	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data						A	K 00020.09	

62349 FABRIC COTTON/DCY JERSEY KNIT GID: BFFSXX
MANF: COTTON INC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	025.9	014.3	0.020		01.50	12.00	T NONE	No test data	No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005556 4

62349 FABRIC COTTON/DCY JERSEY KNIT (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.023		01.34	12.00	T NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

63871 FABRIC COTTON/LYCRA GID: BFXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00061.30	

62386 FABRIC COTTON/POLYESTER GID: BFFSCB

MANF: BEEHIVE CLOTH MILLS

SPEC: ST10U1879

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

ST10U1879-01

TOXICITY

RT	WEIGHT	CURE
K	00123.85	

20729 FABRIC CSPP1 WHITE

....NO TEST DATA AVAILABLE....

64070 FABRIC CWV2/SOLUBOND 1128 GID: BFFSXX

MANF: AKRON CHEMICAL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.010		01.00	12.00	T MOD
X	1	030.0	010.0	0.010		01.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.2E-6	.63	.01	.46	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00009.94	

20379 FABRIC DACRON 15292 GID: BFCBXX

MANF: STERN & STERN

SPEC: ST11D587-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.011			00.40	NONE
X	1	023.8	014.5	0.011		00.57	12.00	T MOD
X	2	025.9	014.3	0.012		00.30	12.00	T MOD
X	1	025.9	014.3	0.012		00.54	12.00	T MOD
X	1	030.0	009.0	0.011		00.51	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-7	.70	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00013.19	

62074 FABRIC DACRON 15453 7.52 OZ/YD GID: BFCDXX

MANF: STERN & STERN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.20	.01		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
No test data		

05847 FABRIC DACRON 601/SILICONE SE7501 GID: BFCKXX

....NO TEST DATA AVAILABLE....

62108 FABRIC DACRON FELT GID: BICBXX

MANF: PIONEER INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.2E-7	.18	.00		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005557 6

05082 FABRIC DACRON WET B4A GID: BFXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.21	.01	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

61977 FABRIC DACRON PACK CLOTH 6.3 OZ GID: BFCBXX

MANF: BALLY RIBBON MILLS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.07	.02		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

62796 FABRIC DACRON S1185 GID: BFXXXX

MANF: GEORGE HARRIS CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.005		02.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62797 FABRIC DACRON S1185/FORM A GID: BFXXXX

MANF: TEXAS TECH UNIV

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.007			05.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62798 FABRIC DACRON S1185/FORM B GID: BFXXXX

MANF: TEXAS TECH UNIV

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.007			06.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62799 FABRIC DACRON S1185/FORM C GID: BFXXXX

MANF: TEXAS TECH UNIV

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.008			05.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62493 FABRIC DACRON WITH RUBBER BUTYL GID: BGCBCZ

MANF: DIAPHRAGM INDUSTRIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.2E-6	1.94	.34		4H-300F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

61385 FABRIC DACRON/SILICONE RUBBER SRD5210 GID: BFDPCB

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.013			01.10	NONE
C	1	023.8	014.5	0.013		00.44	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.4E-6	.89	.34		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	V 00020.94	

61384 FABRIC DACRON/VITON FD5318 GID: BFDECB

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.020			00.10	NONE
X	1	023.8	014.5	0.020		00.17	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005558 8

61384 FABRIC DACRON/VITON FD5318 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.4E-6	1.16	.44		

ODOR

RT	RT WEIGHT	CURE
A	A 00046.39	

TOXICITY

60871 FABRIC DELNET R0709 POLYPROPYL GID: BFCGXX

MANF: W L GORE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.006			00.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	V 00001.03	

TOXICITY

05916 FABRIC DF513/DF202 SILICONE GID: BFDPXX

MANF: FLEXFAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.128			01.80	NONE
B	2	030.0	010.0	0.110		00.02	00.01	NONE
B	1	030.0	010.0	0.110		00.01	06.65	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	.23	.07	.06	

ODOR

RT	RT WEIGHT	CURE
A	A 00020.04	

TOXICITY

69843 FABRIC DISCOVERY 86U101-5 OI LAVENDER BLUE 80% WORSTED WOOL 20% RAYON GID: BFXXXX

MANF: ANTON MAIX FABRICS INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.080		0.40	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20479 FABRIC DPB 65-45 KEVLAR 29 GID: BFJHXX

MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.008			00.10	NONE
X	1	020.9	014.7	0.008		00.66	11.90 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20007 FABRIC DRIGUARD 1227 NYLON/PVC GID: BFCBXX

MANF: ENVIROPAK INC

....NO TEST DATA AVAILABLE....

06533 FABRIC DRIGUARD 1527 POLYESTER GID: BFCBXX

MANF: ENVIROPAK INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.043			02.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20570 FABRIC DUCK COTTON TY 3 GID: BFXXXX

SPEC: CCC-C-419

MANF:

....NO TEST DATA AVAILABLE....

65179 FABRIC DUCK FLEX BLACK GID: BKXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	X 00014.40	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005559 T

65178 FABRIC DUCK FLEX BLUE GID: BKXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00017.50	

01602 FABRIC DUCK GREEN GID: BKXXXX

....NO TEST DATA AVAILABLE....

60163 FABRIC DUCK NYLON CLOTH GID: BKBSXX

MANF: SPEC: MIL-C-3953

....NO TEST DATA AVAILABLE....

60246 FABRIC DUCK NYLON NATURAL GID: BKBSXX

MANF: SPEC: MIL-C-7219T1C1

....NO TEST DATA AVAILABLE....

06294 FABRIC DURETTE 400-11 NOMEX GID: BFBVXX

MANF: FIRESAFE PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.150			00.90	NONE
A	1	025.9	014.3	0.220			01.70	NONE
A	1	030.0	009.0	0.250			01.10	NONE
B	1	030.0	010.0	0.080		00.80	06.80	NONE
A	1	033.0	014.3	0.150			01.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.91	.06	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.51	

65329 FABRIC DURETTE 400-11/7878 NOMEX GID: BFBVXX

MANF: FIRESAFE PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.030		00.40	11.90	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61076 FABRIC DURETTE 400-18 NOMEX NT GID: BFBVXX

MANF: FIRESAFE PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.010			00.10	NONE
C	1	025.9	014.3	0.010		00.39	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00011.04	

61338 FABRIC DURETTE 400-36 NOMEX GID: BFBVXX

MANF: FIRESAFE PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.055			02.20	NONE
A	1	030.0	009.0	0.055			02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61931 FABRIC DURETTE 400-37 NOMEX NT GID: BFBVXX

MANF: FIRESAFE PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.012		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005560 6

61931 FABRIC DURETTE 400-37 NOMEX HT (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	025.9	014.3	0.012		00.47	12.00	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	A 00011.01	

61074 FABRIC DURETTE 400-7 NOMEX HT GID: BFBVXX

MANF: FIRESAFE PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.009			02.50	NONE
I	1	033.0	014.3	0.009		00.50	12.00	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	A 00010.17	

20781 FABRIC DURETTE 420-11 GID: BFXXXX

MANF: FIRESAFE PRODUCTS

....NO TEST DATA AVAILABLE....

63736 FABRIC DURETTE 420-2 GID: BFXXXX

MANF: FIRESAFE PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.012		00.01	00.12	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.2E-6	3.66	.03	2.90	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	K 00022.01	

63737 FABRIC DURETTE 430-13 GID: BFXXXX

MANF: FIRESAFE PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.030		00.00	00.10	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.2E-6	3.74	.01	2.97	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	K 00022.26	

60947 FABRIC DURETTE HCO-2

MANF: FIRESAFE PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.013			01.60	NONE
A	1	030.0	009.0	0.013			01.60	NONE
A	1	033.0	009.0	0.013			01.80	NONE
I	1	040.0	009.0	0.013		00.49	12.00	T SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	A 00009.66	

62327 FABRIC DURVIL/NOMEX GID: BFBVXX

MANF: AVTEX FIBERS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.016		01.21	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0005561 8

Information Handling Services, 2000

62326 FABRIC DURVIL/WOOL GID: BFGZXX
MANF: AVTEX FIBERS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.021		00.68	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80094 FABRIC ELASTIC 0.75 WIDE GID: BFXXXX
MANF: NARROW FABRIC INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	020.2	0.050		01.70	12.00	T MOD
X	1	100.0	020.2	0.050		03.40	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	22.267	

62036 FABRIC ELASTIC 1700 1.0 WIDE GID: BHXXXX
MANF: GEORGE C MOORE CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.059		00.53	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00011.08	

62035 FABRIC ELASTIC 733 1.25 WIDE GID: BHXXXX
MANF: DELTA ELASTIC CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.053		00.35	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00012.04	

62932 FABRIC FACILON 1814 PVC BLUE GID: BFHCXX
MANF: SUN CHEMICAL SPEC: MIL-C-43006BT1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.023			06.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60332 FABRIC FACILON NYLON/VINYL BLU GID: BFCVBS
MANF: SUN CHEMICAL SPEC: MIL-C-43006C

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.023			06.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05386 FABRIC FAIRPRENE VT007 TFE/VITON GID: DOCKXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.020			02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.6E-6	.74	.10		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

62280 FABRIC FARRELL FIBERGLASS GID: BFFVXX
MANF: INDUSTRIAL PLASTICS

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005562 T

62280 FABRIC FARRELL FIBERGLASS (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00020.27	

TOXICITY

20364 FABRIC FELT 5913-07 NOMEX GID: BFBVXX

MANF: FELTERS CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.220			00.30	NONE
X	1	025.9	014.3	0.220		00.05	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	2.96	.05		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.47	

TOXICITY

62545 FABRIC FELT DURETTE BATTING GID: BIXXXX

MANF: FIRESAFE PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.150		00.15	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00019.87	

TOXICITY

65378 FABRIC FELT NYLON 236-006-03 GID: BIBSXX

MANF: NATIONAL FILTER CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.100			00.30	NONE
C	1	030.0	010.0	0.100		00.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.6E-6	2.43	.04	1.92	

ODOR

RT	RT	WEIGHT	CURE
A	K	00022.13	

TOXICITY

02030 FABRIC FG104 BETA F017A FINIS GID: BFXXXX

MANF: OWENS CORNING

....NO TEST DATA AVAILABLE....

62933 FABRIC FIBERGLASS 1450-045 GID: BFFVXX

MANF: PRODESCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.025		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05331 FABRIC FIBERGLASS 2103/108 TFE GID: BFCNIA

SPEC: MIL-I-18746

MANF: T F INDUSTRIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00010.40	

TOXICITY

80155 FABRIC FIBERGLASS NOC

....NO TEST DATA AVAILABLE....

20140 FABRIC FIBERGLASS SILICONE/7010 GID: BFFVDP

MANF: ADEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.068		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0005563 1

Information Handling Services, 2000

20140 FABRIC FIBERGLASS SILICONE/7010 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	023.8	014.5	0.068		00.04	10.00	T SMALL

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.2E-7	1.35	.50		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	A 00010.03	

00777 FABRIC FIBERGLASS STYLE 7628 GID: BFFVXX

MANF: FIBERGLASS REIN INC SPEC: MIL-Y-1140

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.010		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 00022.27	

06570 FABRIC FIBERGLASS/CHLOROPRENE GID: BFGDXX

MANF: AQM

....NO TEST DATA AVAILABLE....

60282 FABRIC FIBERGLASS/SILANE I399

MANF: BURLINGTON

....NO TEST DATA AVAILABLE....

06339 FABRIC FIBERGLASS/SILICONE 03080 GID: BFFVXX

MANF: T F INDUSTRIES SPEC: MIL-Y-1140H

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.041			01.10	NONE
A	1	030.0	009.0	0.041			02.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05365 FABRIC FIBERGLASS/TFE 100S GID: BFFVCN

....NO TEST DATA AVAILABLE....

06319 FABRIC FIBERGLASS/VITON 5707 GID: BFFVDE

MANF: ARMCO INC
BOYD INDUS RUBBER
CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.007			02.20	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	.42	.13		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	K 00020.24	

64977 FABRIC FIBERSLIP B40

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.23	.00	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

62944 FABRIC FLAME RETARDANT GID: BFXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.025			06.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005564 3

20793 FABRIC FLANNEL 545 COTTON WHITE GID: BFFSXX
MANF: CARNEGIE TEXTILE
....NO TEST DATA AVAILABLE....

60934 FABRIC FLANNEL VIRGIN GID: BFFSXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.015		01.58	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06330 FABRIC FLUOREL/GLASS RL3489 GID: BFGDXX
....NO TEST DATA AVAILABLE....

02968 FABRIC FLUOREL/GLASS RL3520 GID: BFGDXX
MANF: RAYBESTOS-MANHATTAN
....NO TEST DATA AVAILABLE....

05116 FABRIC FLUOREL/NYLON V16-30 GID: BFDEBS
....NO TEST DATA AVAILABLE....

05267 FABRIC FLUORGLAS 2812 GID: BFCNXX
MANF: OAK INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.013	0.003		00.80	NONE
A	1	030.0	010.0	0.015	0.003		01.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		70	0.013	02	03
X	PNEU	1500		70	0.013	2	03
Z	MECH	1500	72	70	0.013	2	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.16	.28	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00075.05	

05268 FABRIC FLUORGLAS 2815 TFE/SILICONE GID: BFCNCK
MANF: OAK INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.012	0.003		01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		70		2	04
Z	MECH	1500	72	70		1	01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.8E-6	.67	.16		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00067.77	

20764 FABRIC FR COTTON 7 OZ/SQ YD GID: BFFSXX
MANF: REEVES BROS
WESTERN PIECE DYERS

SPEC: ST11C709-01 ST11C709-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.018			07.10	NONE
A	2	025.9	014.3	0.016			00.10	NONE
A	1	025.9	014.3	0.016			04.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.54	

20008 FABRIC FRL 397.356 NOMEX GID: BFBVXX
MANF: SOUTHERN SILK MILLS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005565 5

62245 FABRIC FYPRO GID: BFJHXX
MANF: DAVID CLARK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.014		00.40	12.10	T NONE
I	1	025.9	014.3	0.013		00.41	12.00	T SMALL
I	1	030.0	009.0	0.014		00.30	12.10	T NONE
I	1	030.0	009.0	0.013		00.36	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62246 FABRIC FYPRO 9805 P46EH GID: BFJHXX
MANF: DAVID CLARK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.011		00.29	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20400 FABRIC FYPRO TREATED NOMEX GID: BFBSXX
MANF: DAVID CLARK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.013			00.30	NONE
C	1	025.9	014.3	0.013		00.39	12.00	T NONE
A	1	025.9	014.3	0.010			02.10	NONE
I	1	030.0	009.0	0.013		00.15	12.00	T NONE
A	1	030.0	009.0	0.010			01.80	NONE
X	1	100.0	008.0	0.011		01.28	12.00	T MOD
I	1	100.0	008.0	0.012		01.09	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.06	.25		

ODOR

RT	RT	WEIGHT	CURE
A	X	00006.23	

TOXICITY

06271 FABRIC GAP FILLER GID: AKHODP
MANF: ROCKWELL

SPEC: MA0605-308 MB0130-068
MB0135-065T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.021			00.20	NONE
B	1	020.9	014.7	0.021		00.50	11.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.2E-7	1.17	.17		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05934 FABRIC GLASS FIBER VARNISHED GID: BFGDXX
MANF:
SPEC: MIL-I-17205
....NO TEST DATA AVAILABLE....

05008 FABRIC GLASS FOR PLASTIC LAMIN GID: BFIAXX
MANF:
SPEC: MB0135-009
....NO TEST DATA AVAILABLE....

06379 FABRIC GLASS PLASTIC COATED GID: BFGDBY
....NO TEST DATA AVAILABLE....

06353 FABRIC GLASS SILICONE SMC1050 GID: DODPFV
MANF: AIRCRAFT PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.075			00.10	NONE

FSG

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005566 7

06353 FABRIC GLASS SILICONE SMC1050 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.075			01.20	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

06285 FABRIC GLASS/ALUMINUM/SILICONE SRGA2218 GID: BBIACK

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.018			02.60	SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62347 FABRIC GLASS/EPOXY L1040-108 GID: BFBGIA

MANF: FORTIN CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.003		00.13	12.00	T NONE
X	1	025.9	014.3	0.003		01.68	12.00	T MOD

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.34	.01		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.16	

64463 FABRIC GLASS/LAMIN 3171 RESIN GID: BGIAXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.030		00.54	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64462 FABRIC GLASS/LAMIN 3171/PT401 GID: BGIAXX

MANF:

SPEC: MIL-S-13865T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.030		00.55	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63528 FABRIC GLASS/NOMEX S2283R GID: BFBVIA

MANF: TEX-TECH IND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.041		00.04	00.10	NONE
C	1	030.0	010.0	0.041		00.07	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62801 FABRIC GLASS/POLYESTER F149 IMPREG GID: BFFVCB

MANF: TREVARNO DIVISION

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.065		00.22	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06089 FABRIC GLASS/PTFE COATED VM3033 GID: BFGDXX

MANF:

SPEC: MBO135-018T2

....NO TEST DATA AVAILABLE....

03266 FABRIC GLASS/SILICONE GID: BEIACK

MANF: CONN HARD RUBBER

SPEC: AMS 3315

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.030			00.15	NONE
A	1	020.9	014.7	0.030			01.90	NONE
X	1	030.0	010.0	0.015		00.19	12.00	T MOD

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00010.07	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005567 9

03301 FABRIC GLASS/SILICONE GID: BGCKIA
MANF: CONN HARD RUBBER SPEC: AMS 3320

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.030			00.10	NONE
A	1	020.9	014.7	0.030			01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.5E-6	1.24	.34		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00010.20	

05264 FABRIC GLASS/SILICONE GID: BFIACK
MANF: KIRKHILL RUBBER SPEC: MIL-C-9084 T4&7 ZZ-R-765 CL 1B GR 50

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.040			00.10	NONE
B	1	023.8	014.5	0.040		00.30	06.70	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00093.67	

05523 FABRIC GLASS/SILICONE GID: DVCKIA
MANF: SIERRACIN/HARRISON SPEC: MIL-C-9084 T2 C3 ZZ-R-765 CL 2B GR 50

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.050			02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05858 FABRIC GLASS/SILICONE GID: BFDPIA
MANF: GENERAL ELECTRIC SPEC: AMS 3345

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.039			02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.71	.27	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05387 FABRIC GLASS/SILICONE 562F GID: BFCKIA
MANF: PERMACEL
....NO TEST DATA AVAILABLE....

05388 FABRIC GLASS/SILICONE 564E GID: BFCKIA
MANF: PERMACEL
....NO TEST DATA AVAILABLE....

05120 FABRIC GLASS/SILICONE AP2363 GID: BFCKIA
MANF: ARROWHEAD PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.023			00.40	NONE
I	1	030.0	009.0	0.011		00.91	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.8E-7	.13	.00		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00024.29	

05119 FABRIC GLASS/SILICONE KSF100-2 GID: CRFVCK
MANF: KIRKHILL RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.043			00.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005568 0

05119 FABRIC GLASS/SILICONE KSF100-2 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.8E-7	.38	.11		

ODOR

RT	RT WEIGHT	CURE
A	A 00035.18	

TOXICITY

61378 FABRIC GLASS/SILICONE SRG1817 GID: BFDPIA

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.017		00.02	12.00	T NONE
C	1	023.8	014.5	0.017		00.33	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.0E-6	.55	.11		

ODOR

RT	RT WEIGHT	CURE
A	V 00035.44	

TOXICITY

03403 FABRIC GLASS/TFE COATED GID: BFIACN

MANF:

SPEC: MB0135-002

....NO TEST DATA AVAILABLE....

06121 FABRIC GLASS/TFE COATED M381-10 GID: BFGDCN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.008			01.00	SMALL
A	1	030.0	009.0	0.009			00.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	K 00094.95	

TOXICITY

69978 FABRIC GORTEX 1/8 TFE FLUOROCARBON JOINT SEALANT

MANF: W L GORE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	2000	72	80	0.100	00	20
Z	MECH	2500	72	80	0.10	2	3
X	PNEU	2500		80	0.100	02	02
X	PNEU	500		80	0.100	01	07

69980 FABRIC GORTEX 1/8 TFE FLUOROCARBON PIPE SEALANT ADHES

MANF: W L GORE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		80	0.060	01	01
Z	MECH	1500	72	80	0.060	01	03
Z	MECH	3000	72	80	0.060	01	01
Z	MECH	4500	72	80	0.060	02	02
X	PNEU	500		80	0.060	01	02
Z	MECH	500	72	80	0.060	01	01
X	PNEU	5000		80	0.060	02	02

20290 FABRIC GORTEX 1883C GID: BFBVXX

MANF: BALLY RIBBON MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.0	010.5	0.015			01.80	NONE
A	1	025.9	014.3	0.015			02.00	NONE
A	1	030.0	009.0	0.015			02.00	NONE
A	1	033.0	014.3	0.015			02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005569 2

20290 FABRIC GORTEX 1883C (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	050.0	010.5	0.015			03.20	SMALL
X	1	075.0	010.5	0.015		00.27	12.00	T MOD
X	1	100.0	016.5	0.015		00.44	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.0E-7	.05	.00		60H-70F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.36	

20287 FABRIC GORTEX 2301 GID: BFBVXX

MANF: BALLY RIBBON MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.009			02.90	SMALL
A	1	030.0	010.0	0.010		00.33	03.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.6E-7	.33	.04		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	A 00011.68	

65447 FABRIC GORTEX P/N L11517 GID: BFCBXX

MANF: W L GORE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.010		01.00	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 00021.13	

63723 FABRIC GORTEX TRICOT/PTFE GID: BFXXXX

MANF: BALLY RIBBON MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.016		01.40	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.4E-6	.25	.03	.05	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 00022.03	

06512 FABRIC HERCULITE 80 NYLON GID: BFAEBS

MANF: HERCULITE CORP SPEC: MIL-C-43006BT2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.023		00.13	12.00	T MOD
I	1	020.9	014.5	0.030		00.17	11.10	T NONE
X	1	020.9	014.7	0.025		00.43	11.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.6E-6	27.88	17.48	.22	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

06357 FABRIC HT-10-41 NOMEX GID: BFBVLJ

MANF: STERN & STERN SPEC: ST11N054-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.013			00.30	MOD
X	1	025.9	014.3	0.013		00.32	12.00	T NONE
S	1	025.9	014.3	0.024			05.20	NONE
S	1	030.0	010.4	0.024			02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005570 9

06357 FABRIC HT-10-41 NOMEX (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.020			00.20	NONE
C	1	030.0	010.0	0.020		00.40	12.00	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	9.0E-6	3.77	.01		

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.93	

06235 FABRIC HT-16-45 NOMEX GID: BFBVXX

MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.008			00.10	NONE
B	1	020.9	014.7	0.008			08.30	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.8E-6	3.36	.01		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

61181 FABRIC HT-195-40 NOMEX GID: BFBVXX

MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.029		00.28	10.00	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00039.34	

05481 FABRIC HT-2002 ARAMID/KNIT MESH GID: FJJHXX

MANF: MOHAWK MILLS SPEC: MB0135-055

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.030		00.48	12.00	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	9.3E-6	3.06	.00		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05707 FABRIC HT-244-36 NOMEX NATURAL GID: BFBVXX

MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.027			01.50	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00038.88	

05081 FABRIC HT-287-45 NOMEX GID: BFBVXX

MANF: STERN & STERN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.17	.02	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00002.34	

65291 FABRIC HT-318-53 NOMEX GID: BFBVXX

MANF: STERN & STERN

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005571 0

65240 FABRIC HT-318-53 NOMEX NATURAL GID: BFBVXX

MANF: STERN & STERN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00021.11	

62945 FABRIC HT-337 NOMEX GID: BFBVXX

MANF: DUPONT
MCDONNELL DOUGLAS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.7	0.010			00.50	NONE
C	1	023.8	014.7	0.010		00.27	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06001 FABRIC HT-46-XX ARAMID WOVEN GID: BFJHXX

MANF: STERN & STERN

SPEC: MB0135-054

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.011			04.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.4E-6	3.70	.04	3.12	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

65129 FABRIC HT-472-40 NOMEX/COTTON GID: BFBVFS

MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.020		00.80	08.60	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65128 FABRIC HT-473-41 NOMEX/COTTON GID: BFBVFS

MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.020		00.80	08.70	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65292 FABRIC HT-5-42 NOMEX GID: BFBVXX

MANF: STERN & STERN

....NO TEST DATA AVAILABLE....

65239 FABRIC HT-5-42 NOMEX NATURAL GID: BFBVXX

MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	015.0	0.006			05.25	NONE
I	1	025.9	014.3	0.006		00.20	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	2.14	.03	1.65	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00026.10	

65238 FABRIC HT-59-62 NOMEX GID: BJBVXX

MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.030			02.00	NONE
X	1	030.0	010.0	0.030		00.20	11.80	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005572 2

05437 FABRIC HT-6-42/NOMEX GID: BFBVXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	019.0	014.3	0.006			02.60	NONE
I	1	023.8	014.5	0.006		00.94	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.2E-6	2.97	.00	2.71	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00005.11	

61180 FABRIC HT-67-42 NOMEX NATURAL GID: BFBVXX

MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.016		00.19	12.00	T NONE
B	2	030.0	010.0	0.020			00.20	NONE
B	1	030.0	010.0	0.020		00.30	11.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00017.77	

05479 FABRIC HT-90-40 NOMEX GID: BFBVGR

MANF: STERN & STERN

SPEC: MIL-C-38351T2C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.023			01.90	NONE
C	2	023.8	014.5	0.011			00.10	NONE
C	1	023.8	014.5	0.011		00.27	12.00	T NONE
C	2	025.9	014.3	0.013			00.30	NONE
C	1	025.9	014.3	0.013		00.23	12.00	T SMALL
I	1	030.0	009.0	0.013		00.20	12.00	T NONE
A	1	030.0	009.0	0.076			03.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-7	3.62	.00		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00012.53	

62362 FABRIC HT-90-40 NOMEX/STN RMVR GID: BFBVGR

MANF: INCREDIBLE INC
STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.4	0.010		00.41	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05080 FABRIC HT-96 NOMEX RESIN TREAT GID: BFBVXX

MANF: STERN & STERN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.39	.07	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00002.06	

65143 FABRIC HT-96-62G NOMEX NATURAL GID: BMBVXX

MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.010			04.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	4.44	.09	3.02	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005573 4

60488 FABRIC KELVAR 29 GID: BMJHXX

MANF: BALLY RIBBON MILLS
FABRIC DEVELOPMENT
FABRIC RESEARCH LAB
GOODYEAR
PREFORM INC
STERN & STERN

SPEC: DPB 3837
MB0135-053
ST11K742

DPB 4-46
RF-443
STYLE DPB-38-37

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.015			01.00	NONE
A	1	020.9	014.7	0.017			01.40	NONE
B	2	023.8	014.5	0.018		00.00	00.00	NONE
B	1	023.8	014.5	0.018		00.02	11.40	NONE
A	1	023.8	014.5	0.027			01.80	NONE
C	2	025.9	014.3	0.010		00.14	12.00	T NONE
C	1	025.9	014.3	0.010		00.89	12.00	T NONE
A	1	025.9	014.3	0.011			01.20	NONE
A	1	030.0	009.0	0.040			02.00	NONE
A	1	030.0	009.0	0.011			02.40	NONE
A	1	031.0	010.0	0.055			00.40	SMALL
X	1	100.0	006.2	0.055		00.03	12.00	T MOD

FSC

RT	FLUID NAME
A	AMMONIA

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.25	.17	.71	

ODOR

RT	RT	WEIGHT	CURE
A	V	00004.66	

TOXICITY

61111 FABRIC KEVLAR GID: BMJHXX

MANF: BALLY RIBBON MILLS

SPEC: EI 4053

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.14	.24		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

80030 FABRIC KEVLAR 102-123-2 COATED VITON GID: BFJHDE

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.009			04.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	22.282	

TOXICITY

20329 FABRIC KEVLAR 152 KNIT GID: BFJHXX

MANF: FABRIC DEVELOPMENT

SPEC: ST11K113-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010			03.50	NONE
X	1	030.0	010.4	0.012		00.15	12.00	T NONE
X	2	033.0	014.3	0.010		00.20	12.00	T NONE
X	1	033.0	014.3	0.010		00.19	12.00	T MOD

FSC

RT	FLUID NAME
A	AMMONIA

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	3.97	.09		

ODOR

RT	RT	WEIGHT	CURE
A	A	00006.53	

TOXICITY

62803 FABRIC KEVLAR 1813-2 WITH VITON GID: BFJHXX

MANF: BALLY RIBBON MILLS
PELMOR LABORATORIES

SPEC: MIL-R-83248C2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.062			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005574 6

62803 FABRIC KEVLAR 1813-2 WITH VITON (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00011.87	

20641 FABRIC KEVLAR 2176

MANF: FABRIC RESEARCH LAB

....NO TEST DATA AVAILABLE....

62804 FABRIC KEVLAR 29/774 GID: BFJHXX

MANF: SOUTHERN SILK MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.030			02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62805 FABRIC KEVLAR 29/H7000-605 GID: BFJHXX

MANF: PRODESCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.050		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60853 FABRIC KEVLAR 343 GID: BFJHXX

MANF: CLARK SCHWEBEL CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.010			00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60135 FABRIC KEVLAR 49 GID: BFJHXX

MANF: BURLINGTON

SPEC: AMS 3902

STYLE 26435

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.33	.08	1.61	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.30	

62806 FABRIC KEVLAR 49 STYLE 26435 GID: BFJHXX

MANF: BURLINGTON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025		00.10	02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05274 FABRIC KEVLAR 49 T120/SILICONE 7021G GID: CHCKJM

MANF: ARROWHEAD PRODUCTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.3E-6	.37	.02		8H-400F- 24H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05068 FABRIC KEVLAR 49/EPOXY GID: FJJHBG

MANF: STRUCTURAL COMPOSITES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.125			01.50	NONE
A	1	030.0	009.0	0.125			01.75	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.36	.05	1.01	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	106.30	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005575 8

62807 FABRIC KEVLAR 9M03893/1813 GID: BFJHXX

MANF: BALLY RIBBON MILLS
PRODESCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.040			01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80018 FABRIC KEVLAR EPOXY PANEL GID: BFJHBG

MANF: STRUCTURAL COMPOSITES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	10.403	

63284 FABRIC KEVLAR GAC-RF443 GID: BFJHXX

MANF: PRODESCO SPEC: 9M03839

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00187.20	

62802 FABRIC KEVLAR RF443/TAPE RF282 GID: BFJHXX

MANF: GOODYEAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.125			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20342 FABRIC KEVLAR STYLE 202 3.2 OZ GID: BFXXXX

MANF: FABRIC DEVELOPMENT

....NO TEST DATA AVAILABLE....

61705 FABRIC KEVLAR STYLE FDI043 GID: BFJHXX

MANF: FABRIC DEVELOPMENT SPEC: STI1K580-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.007			00.60	NONE
C	1	025.9	014.3	0.007		00.12	12.00 T	NONE
I	2	100.0	020.2	0.007		00.68	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	3.91	.11		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00006.83	

62037 FABRIC KEVLAR U 2209 GID: BFJHXX

MANF: BALLY RIBBON MILLS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.9E-7	2.94	.16		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05117 FABRIC KEVLAR/FLUOREL GID: BFEFCB

MANF: MOSITES RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.011		00.00	00.00	NONE
A	1	023.8	014.5	0.011			01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.1E-7	1.02	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00015.13	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005576 T

20317 FABRIC KEVLAR/NOMEX STYLE 145 GID: BFBVJH

MANF: FABRIC DEVELOPMENT SPEC: ST11G052-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.012			00.10	NONE
C	1	023.8	014.5	0.012		00.07	12.00	T NONE
C	2	025.9	014.3	0.012			00.60	NONE
C	1	025.9	014.3	0.012		00.09	12.00	T NONE
I	2	100.0	020.2	0.012		00.29	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
B	MECH	50	72	120	0.013	0	20
I	MECH	50	72	120	0.013	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.7E-6	3.52	.18		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00010.64	

62808 FABRIC KEVLAR/NYLON GID: BFJHBX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.030		00.40	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

60453 FABRIC KYNOL GID: BFXXXX

MANF: CARBORUNDUM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.040			03.60	NONE
A	1	030.0	009.0	0.040			03.70	NONE
A	1	033.0	009.0	0.040			03.80	NONE
I	1	040.0	009.0	0.040		00.13	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.98	.36	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.25	

20496 FABRIC LYCRA SPANDEX GID: BHFWXX

MANF: DARLINGTON FABRICS SPEC: ST11K609/ILC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.018		00.20	12.00	T SMALL
X	1	025.9	014.3	0.018		01.27	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.6E-7	1.92	.30		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00021.81	

80143 FABRIC M11673 ALUMINIZED POLYURETHANE COATED NYLON

MANF: REEVES BROS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.016		00.10	12.00	T SMALL
X	1	025.9	014.3	0.016		00.50	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	22.055	

65194 FABRIC M11673/NYLON/URETHANE GID: BFCQXX

MANF: AIR CRUISERS CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.020			04.30	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005577 1

05941 FABRIC M380-3 FIBERGLASS/TFE GID: BGFVCN

MANF: OAK INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003			01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
V	00010.60	

20432 FABRIC MARQUISETTE NYLON N-44 GID: BFBSXX

MANF: ADVANCED NETTING SPEC: ST11M039

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.007		00.39	12.00	T NONE
B	1	025.9	014.3	0.007			08.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.2E-7	1.52	.01		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00004.73	

61930 FABRIC MODACRYLIC 6901-1151 GID: BFAKAD

MANF: J P STEVENS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.016			00.10	NONE
C	1	025.9	014.3	0.016		00.57	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00012.99	

65334 FABRIC MOLESKIN

MANF: AMERICAN WHITE CROSS LABS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	20	72	70	0.030	0	20
I	MECH	20	72	70	0.030	0	20

61940 FABRIC MULTI FIL G1106-80MZL GID: BFXXXX

MANF: DARLINGTON FABRICS SPEC: ST11N117-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.023		00.19	12.00	T MOD
X	1	025.9	014.3	0.023		00.73	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.92	.37		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00008.59	

85502 FABRIC MX2600/FM5504 SILICA PHENOLIC

MANF: FIBERITE/US POLYMERIC SPEC: STW5-2652

....NO TEST DATA AVAILABLE....

85503 FABRIC MXB6020/FM5755 GLASS PHENOLIC

MANF: FIBERITE/US POLYMERIC SPEC: STW5-2651

....NO TEST DATA AVAILABLE....

20476 FABRIC NAMETAGS GID: CNBVXX

MANF: HOLICKS INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00024.57	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005578 3

64930 FABRIC NARMCO 3200/120 GID: BFFVXX
MANF: NARMCO
....NO TEST DATA AVAILABLE....

60338 FABRIC NARMCO 506 GLASS PHENOL GID: BFGDBX
MANF: NARMCO
....NO TEST DATA AVAILABLE....

20310 FABRIC NEOPRENE RIPSTOP COATED GID: BGBSDB
MANF: CHEMPRENE SPEC: ST12N083-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
C	2	023.8	014.5	0.008			00.40		NONE
C	1	023.8	014.5	0.008		00.82	12.00	T	NONE
C	2	025.9	014.3	0.009			00.20		NONE
C	1	025.9	014.3	0.009		01.40	12.00	T	NONE

FSC

RT	FLUID NAME
X	AMMONIA

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.2E-7	1.43	.36		

ODOR

RT	
A	K

TOXICITY

RT	WEIGHT	CURE
	00020.17	

61701 FABRIC NEOPRENE/NYLON 18540-33 GID: BGBSDB
MANF: A D LITTLE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.006			03.90	NONE
A	1	031.0	010.0	0.006			05.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	
A	X

TOXICITY

RT	WEIGHT	CURE
	00013.02	

61056 FABRIC NEOPRENE/NYLON CRP21757 GID: BFDBBS
MANF: CHEMPRENE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.019			10.20	NONE
A	1	023.8	014.5	0.019			05.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	
A	K

TOXICITY

RT	WEIGHT	CURE
	00036.82	

60785 FABRIC NETTING/POLYPROPYLENE GID: BLCGXX
MANF: SCOTT AVIATION SPEC: NAS-9-15246

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	
A	K

TOXICITY

RT	WEIGHT	CURE
	00034.92	

06594 FABRIC NICALON SILCN CARB INOR GID: BFCKXX
MANF: NIPPON CARBON CO
....NO TEST DATA AVAILABLE....

20363 FABRIC NO T-261-36 TEFLON GID: BFCNXX
MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
							04.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005579 5

20363 FABRIC NO T-261-36 TEFLON (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.009			03.00	NONE
X	2	033.0	014.3	0.010			00.20	NONE
X	1	033.0	014.3	0.010		00.46	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.02	.00		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00014.83	

65500 FABRIC NOMEX 0049 60% FP/WP GID: BGBVXX

MANF: TRAVIS MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.030		00.00	00.00	NONE
C	1	025.9	014.3	0.030		01.10	12.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20642 FABRIC NOMEX 200 DENIER

MANF: DUPONT

....NO TEST DATA AVAILABLE....

20096 FABRIC NOMEX 2002/FLUOROSILICONE GID: DODGXX

MANF: ARROWHEAD PRODUCTS SPEC: MIL-R-25988

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.040			10.50	NONE
I	1	020.9	014.7	0.040		00.15	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60882 FABRIC NOMEX 2PLY GID: BFBVXX

MANF: STERN & STERN SPEC: ST11N054-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.024			02.50	NONE
A	1	030.0	009.0	0.025			02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00045.22	

60881 FABRIC NOMEX 2PLY/FELT-1PLY GID: BFBVXX

MANF: DRYCORE FELT CO SPEC: ST11N054-02 ST11N105
STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.105			01.80	SMALL
A	1	030.0	009.0	0.105			01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00072.65	

61638 FABRIC NOMEX 3 ARAMD/NO FINISH GID: BFJHXX

MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.071		00.05	12.00	T NONE
C	1	025.9	014.3	0.071		00.90	12.00	T NONE
I	1	030.0	010.0	0.071		00.90	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.3E-6	2.79	.01	1.74	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.43	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005580 1

80050 FABRIC NOMEX 3 NO-MO-STAT WITH STAINLESS STEEL NAVY GID: BFBVXX

MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.025		00.09	12.00	T NONE
C	1	025.9	014.3	0.025		1.9	12.00	T NONE
I	1	030.0	010.0	0.025		2.0	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	22.253	

61637 FABRIC NOMEX 3 WICKWELL FINISH GID: BFJHXX

MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.077		00.05	12.00	T SMALL
C	1	025.9	014.3	0.077		00.90	11.90	T SMALL
I	1	030.0	010.0	0.077		00.90	11.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.3E-6	2.03	.07	1.86	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.37	

61639 FABRIC NOMEX 3/SCOTCHGARD COATED GID: BFBVXX

MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.075		00.00	00.00	NONE
C	1	025.9	014.3	0.075		02.40	12.00	T NONE
C	2	025.9	014.3	0.125			00.10	NONE
C	1	025.9	014.3	0.125		01.00	12.20	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61689 FABRIC NOMEX 3/ZEPEL FINISH GID: BFJHBV

MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.140		00.90	11.80	T NONE
I	1	030.0	010.0	0.140		01.30	11.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.29	

61832 FABRIC NOMEX 30939 2.5OZ BROWN GID: BFBVXX

MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.004		00.98	12.00	T NONE
X	1	023.8	014.5	0.004		01.04	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.4E-7	2.90	.03		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00004.22	

61834 FABRIC NOMEX 30939 2.5OZ ORNG GID: BFBVXX

MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.004			00.20	NONE
C	1	023.8	014.5	0.004		01.07	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005581 3

61834 FABRIC NOMEX 30939 2.5OZ ORNG (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.0E-7	2.86	.01		

ODOR

RT	RT WEIGHT	CURE
A	A 00004.23	

TOXICITY

61833 FABRIC NOMEX 30939 2.5OZ WHITE GID: BFBVXX

MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.004			00.20	NONE
C	1	023.8	014.5	0.004		00.63	11.90	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	8.0E-7	3.41	.01		

ODOR

RT	RT WEIGHT	CURE
A	V 00004.71	

TOXICITY

05781 FABRIC NOMEX 410 GID: BFBVXX

MANF: SPEC: MIL-I-24204

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.05	.01	.02	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20114 FABRIC NOMEX 410 KAPTON/ML GID: BFBVXX

....NO TEST DATA AVAILABLE....

80190 FABRIC NOMEX 6 OZ WASHED IN BOLD 3 TWICE AND DRIED WITH BOUNCE TWICE GID: BFXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.011		1.1	12.00	T SMALL
I	1	030.0	010.0	0.011		1.3	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61964 FABRIC NOMEX 7.5 OZ/ZEPEL GID: BFBVXX

MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.020			02.70	NONE
C	2	030.0	010.0	0.067			00.40	NONE
C	1	030.0	010.0	0.067		0.4	12.10	T NONE
I	1	033.0	014.3	0.020		00.46	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	K 00028.31	

TOXICITY

06227 FABRIC NOMEX 7878 G650 GID: BFFSXX

MANF: DUPONT SPEC: MIL-T-43636/1E
NOAH LAMPORT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.016			00.30	NONE
C	1	025.9	014.3	0.016		00.54	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00019.98	

TOXICITY

61582 FABRIC NOMEX 7878 G650/FC5 GID: BFBVXX

MANF: NOAH LAMPORT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.018			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005582 5

61582 FABRIC NOMEX 7878 G650/FC5 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	025.9	014.3	0.018		00.20	12.00	T NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

20569 FABRIC NOMEX 7878-18 BLUE GID: BFBVXX

MANF: KLOPMAN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.014			00.60	NONE
C	1	023.8	014.5	0.014		00.34	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
	No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	0.8E-6	2.87	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00013.57	

62102 FABRIC NOMEX 7878/POLYESTER954 GID: BFCBBV

MANF: ROCKWELL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.071		00.33	11.90	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
	No test data						

65402 FABRIC NOMEX 863 TWILL GID: BFBVXX

MANF: MARLING & EVANS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.020			01.00	NONE
C	1	030.0	010.0	0.020		00.40	12.00	T NONE
A	2	030.0	010.0	0.040			00.10	NONE
A	1	030.0	010.0	0.040		00.20	05.10	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
	No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-6	3.64	.06	3.24	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00021.35	

65413 FABRIC NOMEX 863/3 TWILL 2X2 GID: BFBVXX

MANF: MARLING & EVANS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.7	0.020		00.30	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
	No test data						

65237 FABRIC NOMEX 90043/46 GID: BFBVXX

MANF: BURCOTT MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	015.0	0.010		00.17	07.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
	No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00031.80	

61593 FABRIC NOMEX 9476 GID: BFBVXX

MANF: BALLY RIBBON MILLS

SPEC: MIL-T-5038T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.0	010.5	0.018			01.90	NONE
A	1	025.0	010.5	0.017			01.70	NONE
I	1	025.9	014.3	0.018		00.30	12.00	T NONE
I	1	030.0	010.5	0.019		00.45	12.00	T SMALL
I	1	035.0	010.5	0.018		00.30	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
	No test data						

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005583 7

61593 FABRIC NOMEX 9476 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	050.0	010.5	0.018		00.90	12.00	T SMALL
X	1	100.0	016.5	0.018		02.32	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.0E-7	3.12	.04		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.15	

62492 FABRIC NOMEX 98379 GID: BFBVXX
MANF: L TRAVIS TEXTILES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.029			01.60	NONE
A	1	030.0	009.0	0.029			02.50	NONE
A	1	033.0	009.0	0.029			01.90	NONE
A	1	040.0	009.0	0.029			04.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65268 FABRIC NOMEX ARAMID 3/0049 6OZ GID: BFBUXX
MANF: TRAVIS MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.020			00.10	NONE
C	1	025.9	014.3	0.020		01.00	12.00	NONE
I	1	030.0	010.0	0.030		01.20	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00021.09	

65348 FABRIC NOMEX ARAMID FR P/N E-2 GID: 7BGBVX
MANF: DUPONT SPEC: MA0105-330

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.050			00.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00030.13	

65198 FABRIC NOMEX ARAMID NAVY BLUE GID: BFBVXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.100			02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00039.19	

63478 FABRIC NOMEX BLUE FLIGHT SUIT GID: BFBVXX
MANF: FLIGHT SUITS LTD
GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.012		00.40	12.10	T NONE
I	1	025.9	014.3	0.010		01.00	12.00	T NONE
I	1	025.9	014.3	0.020		00.60	12.00	T NONE
I	1	030.0	010.0	0.012		00.10	12.80	T NONE
I	1	030.0	010.0	0.002		00.50	12.20	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005584 9

62809 FABRIC NOMEX C4270 GID: BFBVXX
MANF: SOUTHERN SILK MILLS

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
I	1	023.8	014.5	0.030		00.15	12.00 T	NONE	No test data		No test data						

06362 FABRIC NOMEX COATED WITH SCOTCHGARD FC4101 GID: BFBVGR
SPEC: MIL-C-38351T2C1
MANF: 3M CO
STERN & STERN

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
C	1	025.9	014.3	0.013		00.39	12.00 T	NONE	No test data		No test data						
C	2	025.9	014.3	0.012			00.20	NONE									

80247 FABRIC NOMEX COVERALL (WASH/DRIED 25 TIMES) GID: BFXXXX
MANF: BARRIER-WEAR

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.010			03.00	NONE	No test data		No test data						
I	1	030.0	010.0	0.039		00.90	25.50 T	NONE									
I	1	030.0	010.0	0.020		00.60	19.00 T	NONE									

65132 FABRIC NOMEX DENIM LAUNDERED GID: BFBVXX
MANF: SOUTHERN MILLS

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.030			05.54	SMALL	No test data		No test data						
X	1	025.9	014.3	0.030		00.40	12.00 T	MOD									
X	2	030.0	010.0	0.030			00.20	NONE									
X	1	030.0	010.0	0.030		00.40	12.00 T	MOD									

80081 FABRIC NOMEX FDC 307 F/WP GID: BFBVXX
SPEC: MPP-105M330M01 MPS-MA-0105-330
MANF:

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	030.0	010.0	0.007		00.00	00.00	NONE	No test data		No test data						

63926 FABRIC NOMEX FELT X-547 GID: BFBXXX
MANF: W S LIBBEY

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
C	2	030.0	010.0	0.060		00.02	00.50	NONE	No test data		No test data						
C	1	030.0	010.0	0.060		00.20	12.00 T	NONE									

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	K	00022.81	

62810 FABRIC NOMEX GAC-RF-444 GID: BFBVXX
MANF: GOODYEAR

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	030.0	009.0	0.040			03.80	NONE	No test data		No test data						

20341 FABRIC NOMEX HF9254 3.2 OZ GID: BFBVXX
SPEC: ST11N307-01
MANF: STERN & STERN

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
C	2	025.9	014.3	0.009			00.70	NONE	No test data		No test data						

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005585 0

20341 FABRIC NOMEX HF9254 3.2 OZ (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	025.9	014.3	0.009		00.69	12.00	T NONE
X	2	100.0	020.2	0.009		00.42	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	3.36	.00		

ODOR

RT	RT	WEIGHT	CURE
A	A	00006.94	

TOXICITY

85448 FABRIC NOMEX HT-45-55 WITH DC3140 RTV COATING ON ONE EDGE GID: BFXXXX

MANF: ADVANCED EXCELLO PROCESS/DOW CORNING SPEC: WIT-280RM WIT-412RM WIT-541RM WIT-304RM WIT-482RM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.009		00.21	12.0	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85447 FABRIC NOMEX HT-45-55 WITH DYE-AQUA-SET TEXTILE INK WITH DC3140 RTV COATING ON ONE EDGE

MANF: ADVANCED EXCELLO PROCESS/DOW CORNING SPEC: WIT-280RM WIT-412RM WIT-541RM WIT-304RM WIT-482RM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.5	0.009		00.21	11.0	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	35.8	

TOXICITY

61480 FABRIC NOMEX HT-49 GID: BFBVXX

MANF: STERN & STERN SPEC: MBO135-054

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.010			00.20	NONE
C	1	023.8	014.5	0.010		00.45	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.8E-6	3.12	.01		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

20294 FABRIC NOMEX HX-6157 SIZE F GID: EDBVXX

MANF: BELDEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3			03.78	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	7.22	1.72		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.00	

TOXICITY

06100 FABRIC NOMEX K-GUARD CLR#21302 GID: BFBVXX

MANF: CATALINA PACIFIC TEX SPEC: MAO105-330

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.018			02.40	NONE
A	1	033.0	014.3	0.018			02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.2E-7	3.59	.03		

ODOR

RT	RT	WEIGHT	CURE
A	V	00020.17	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005586 2

64805 FABRIC NOMEX K-GUARD/ADP/KEL-F GID: BFBVXX

MANF: KLOPMAN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.015			01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20266 FABRIC NOMEX NON-WOVEN 141-329 GID: BFBVXX

MANF: KENDALL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.001		00.38	12.00 T	NONE
X	1	023.8	014.5	0.001		02.13	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00001.30	

06476 FABRIC NOMEX RED 5-502 FP/WP GID: BFBVXX

MANF: L TRAVIS TEXTILES

SPEC: MA0105-330

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.017			02.20	NONE
A	1	030.0	009.0	0.017			02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.01	

62811 FABRIC NOMEX RF444/TAPE RF282 GID: BFBVXX

MANF: GOODYEAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.116			01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65114 FABRIC NOMEX S/470 LAUNDERED GID: BFBVXX

MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.020			03.60	NONE
X	1	025.9	014.3	0.020		01.40	12.00 T	MOD
X	2	030.0	010.0	0.020		00.09	12.00	MOD
X	1	030.0	010.0	0.020		02.10	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20292 FABRIC NOMEX S2352NBR FILTER GID: BFBVXX

MANF: GLOBE ALBANY CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00007.16	

60709 FABRIC NOMEX S470/ZEPEL 86900 GID: BFBVXX

MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.020			03.90	NONE
A	1	025.9	014.3	0.043		00.00	00.00	NONE
I	1	025.9	014.3	0.018		00.40	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00136.11	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005587 4

65046 FABRIC NOMEX S619 GID: BKBVXX
MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.030			00.10	NONE
X	1	020.9	014.7	0.030		01.00	07.70	NONE
X	2	025.9	014.3	0.030		00.09	12.00	T MOD
X	1	025.9	014.3	0.030			06.00	NONE
X	2	030.0	010.0	0.030		00.09	09.90	MOD
X	1	030.0	010.0	0.030		01.50	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65335 FABRIC NOMEX S619/ARAMID GRN GID: BFBVXX
MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.040			05.10	NONE
C	2	025.9	014.3	0.040		00.09	12.00	T SMALL
C	1	025.9	014.3	0.040		01.20	12.00	T SMALL
C	2	030.0	010.0	0.040		00.09	12.00	T SMALL
C	1	030.0	010.0	0.040		01.40	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20792 FABRIC NOMEX S619/ZEPEL 69878 GID: BFBVXX
MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.034		00.00	00.00	NONE
I	1	023.8	014.5	0.023		00.08	11.90	T NONE
A	1	025.8	014.3	0.034		00.00	00.00	NONE
I	1	025.9	014.3	0.025		00.20	12.00	T NONE
A	1	033.2	015.5	0.034		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00112.85	

TOXICITY

20575 FABRIC NOMEX SIMPLEX GID: BFBVXX
MANF: SOUTHERN SILK MILLS SPEC: MIL-C-81393A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.040			00.20	MOD
X	1	025.9	014.3	0.040		00.36	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	2.88	.00		

ODOR

RT	RT	WEIGHT	CURE.
A	A	00020.03	

TOXICITY

20568 FABRIC NOMEX TRICOT STYLE 240 GID: BFBVXX
MANF: SOUTHERN SILK MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.022		00.06	12.00	T NONE
C	1	025.9	014.3	0.022		00.59	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.7E-6	2.15	.00		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.01	

TOXICITY

62361 FABRIC NOMEX TWILL 6.5 OZ GID: BFBVXX
MANF: NASA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.059			05.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005588 6

61765 FABRIC NOMEX TWILL 60Z NATURAL GID: BFBVXX

MANF: KLOPMAN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.012			00.20	MOD
X	1	023.8	014.5	0.012		08.53	12.00	T NONE
I	1	025.9	014.3	0.011		1.0	12.00	T NONE
I	1	030.0	010.0	0.011		1.0	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	8.0E-7	4.00	.05		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00010.91	

61830 FABRIC NOMEX TWILL 60Z BLACK GID: BFBVXX

MANF: KLOPMAN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.014			00.20	NONE
C	1	023.8	014.5	0.014		00.50	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.0E-7	2.70	.01		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00012.48	

61831 FABRIC NOMEX TWILL 60Z GOLD GID: BFBVXX

MANF: KLOPMAN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.014			00.20	NONE
C	1	023.8	014.5	0.014		00.43	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	0.8E-6	3.34	.00		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	V 00011.74	

61829 FABRIC NOMEX TWILL 60Z RED GID: BFBVXX

MANF: KLOPMAN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.014		00.09	12.00	T NONE
C	1	023.8	014.5	0.014		00.52	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.4E-7	2.74	.02		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	A 00012.08	

60946 FABRIC NOMEX TWILL 98379 6 OZ. GID: BFBVXX

MANF: L TRAVIS TEXTILES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.015		00.16	12.00	T NONE
I	1	030.0	009.0	0.015			12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	A 00018.37	

06293 FABRIC NOMEX TWILL POLYI GID: BFBVXX

MANF: PUTNAM MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.035			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005589 8

06293 FABRIC NOMEX TWILL POLYI (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	025.9	014.3	0.035		00.32	12.00	T NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	X	00020.81	

TOXICITY

62229 FABRIC NOMEX WITH ZEPEL/ARMALON GID: BFBVXX

MANF: DUPONT
SOUTHERN MILLS

SPEC: ST11A830-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.031			01.10	NONE
A	1	030.0	009.0	0.031			00.70	NONE
B	1	033.0	009.0	0.031			07.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62231 FABRIC NOMEX WITH ZEPEL/ARMALON/URETHANE COATED NY GID: BFBVCQ

MANF: DUPONT
KENYON PIECE DYEWORKS
SOUTHERN MILLS

SPEC: ST11A8 0-01 ST12N084-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.037			01.30	NONE
A	1	030.0	009.0	0.037			00.20	NONE
A	1	033.0	009.0	0.037			00.60	NONE
A	1	040.0	009.0	0.037			01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65066 FABRIC NOMEX-BLUE WITH FC4101-C16 GID: BGBVXX

MANF: 3M CO
ROCKWELL

SPEC: MAO105-330

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.070			04.80	NONE
C	1	030.0	010.0	0.070		01.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	X	00043.68	

TOXICITY

64058 FABRIC NOMEX-KEVLAR/TFE/GORTEX GID: BFBVJH

MANF: W L GORE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	030.0	010.0	0.025		0.60	09.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00022.03	

TOXICITY

62227 FABRIC NOMEX/ARMALON BACKING GID: BFBVXX

MANF: DUPONT
L TRAVIS TEXTILES

SPEC: ST11A830-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.027			01.20	NONE
A	1	030.0	009.0	0.027			01.10	NONE
A	1	033.0	009.0	0.027			01.60	NONE
A	1	040.0	009.0	0.027			10.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005590 4

62230 FABRIC NOMEX/ARMALON/URETHANE COATED NY GID: BFBVCQ
SPEC: ST11A830-01 ST12N084-01
MANF: DUPONT
KENYON PIECE DYEWORKS
L TRAVIS TEXTILES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.037			01.10	NONE
A	1	030.0	009.0	0.037			00.80	NONE
A	1	033.0	009.0	0.037			01.00	NONE
A	1	040.0	009.0	0.037			01.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05848 FABRIC NOMEX/BETA GLASS 2458N GID: BFBVHL
MANF: GLOBE ALBANY CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.037			00.10	NONE
C	1	023.8	014.5	0.037		00.11	12.00 T	NONE
C	2	025.9	014.3	0.072			00.30	NONE
C	1	025.9	014.3	0.072		00.13	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	3.33	.07		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00019.44	

65045 FABRIC NOMEX/DENIM BLUE GID: BFBVXX
MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.020			03.30	NONE
X	1	025.9	014.3	0.020		00.40	12.00 T	MOD
X	2	030.0	010.0	0.020			00.20	NONE
X	1	030.0	010.0	0.020		00.40	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62023 FABRIC NOMEX/TEF FILM/NOMEXWEB GID: BFCOBV
MANF: SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3				01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20713 FABRIC NOMEX/TFE COATED GID: BFBVCN
MANF: W L GORE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.009			04.80	NONE
C	2	025.9	014.3	0.008			01.10	NONE
C	1	025.9	014.3	0.008		01.11	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00019.73	

62228 FABRIC NOMEX/URETHANE COATED NYLON B GID: FBVCQ
SPEC: ST12N084-01
MANF: KENYON PIECE DYEWORKS
L TRAVIS TEXTILES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.027			00.30	NONE
A	1	030.0	009.0	0.027			05.90	NONE
A	1	033.0	090.0	0.027			01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005591 6

62228 FABRIC NOMEX/URETHANE COATED NYLON B (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	040.0	090.0	0.027		00.19	11.50	T SMALL

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

61061 FABRIC NOMEX/VELCRO/FC4101 GID: BFBVXX

MANF: STERN & STERN
VELCRO CORP

SPEC: MIL-C-3851T2C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.124		00.21	10.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05371 FABRIC NOMEX/VITON 5713 GID: CHDEBV

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.014			02.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.6E-6	1.36	.07		

ODOR

RT	RT	WEIGHT	CURE
	V	00008.72	

TOXICITY

20406 FABRIC NOMEX/ZEPEL COATED GID: BFBVXX

MANF: SOUTHERN MILLS

SPEC: ST11C834-01 ST11N701-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.077			02.30	NONE
A	1	025.9	014.3	0.044			01.20	NONE
A	1	025.9	014.3	0.030			01.70	NONE
I	1	025.9	014.3	0.016		00.32	12.00	T NONE
A	1	030.0	009.0	0.030			01.50	NONE
I	1	030.0	009.0	0.016		00.32	12.00	T NONE
A	1	030.0	009.0	0.045			03.30	NONE
A	1	033.0	014.3	0.077			02.90	NONE
A	1	033.0	014.3	0.044			02.70	NONE
A	1	033.0	009.0	0.030			01.80	NONE
A	1	040.0	009.0	0.030			04.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.1E-6	3.28	.01		24H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	A	00035.56	

TOXICITY

62309 FABRIC NOR-FAB 400/8PT22 GID: BFXXXX

MANF: AMATEX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.030			04.30	NONE
C	1	025.9	014.3	0.030		00.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.38	.00	.94	

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.31	

TOXICITY

69959 FABRIC NS456 ALUMINIZED POLYURETHANE NYLON

MANF: URETEK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.010		0.1	12.00	T MOD
X	1	025.9	014.3	0.010		0.6	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	21.921	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005592 8

01942 FABRIC NYLON GID: BFBSXX
MANF: QSL — SPEC: MB0135-021 — MIL-C-7350T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.5	0.025		00.40	12.00 T	MOD
X	2	020.9	014.7	0.025			00.50	MOD
X	1	020.9	014.7	0.027			03.00	MOD

FSC: No test data

OXYGEN COMP: No test data

80236 FABRIC NYLON 2257 NEOPRENE COATED BONDED WITH SHORE CHEMICAL UBS-N1030 ADHESIVE AND NEOPRENE COATED NYLON TAP GID: BNXXXX
MANF: ISI

THERMAL VACUUM STABILITY: No test data

ODOR: RT B — TOXICITY: RT WEIGHT 20.925 — CURE 12H-120F-12.4psia

20309 FABRIC NYLON 6611 OXFORD YELLOW GID: BFBSXX
MANF: KENYON PIECE DYEWORKS — SPEC: ST12N084-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.010		00.46	12.00 T	NONE
X	2	023.8	014.5	0.012		00.11	12.00 T	NONE
X	1	023.8	014.5	0.012		00.63	12.00 T	NONE
X	1	030.0	009.0	0.010		00.85	12.00 T	MOD

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.2E-7	1.14	.13		

ODOR: RT A — TOXICITY: RT A WEIGHT 00015.43 — CURE

60989 FABRIC NYLON A2598/15 LT BLUE GID: BFBVXX
MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.006			02.30	NONE
X	1	025.9	014.3	0.006		01.03	12.00 T	MOD

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY: No test data

ODOR: RT A — TOXICITY: RT K WEIGHT 00012.57 — CURE

20338 FABRIC NYLON A2634/B 3.8 OZ GID: BFBSXX
MANF: STERN & STERN — SPEC: ST11N142-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.008			00.40	NONE
C	1	025.9	014.3	0.008		00.62	12.00 T	NONE

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	1.41	.01		

ODOR: RT A — TOXICITY: RT V WEIGHT 00007.28 — CURE

60626 FABRIC NYLON A5691 GID: BFBVXX
MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.006			04.00	MOD
X	1	025.9	014.3	0.006		00.40	12.00 T	NONE

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY: No test data

ODOR: RT A — TOXICITY: RT A WEIGHT 00020.26 — CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005593 T

20232 FABRIC NYLON BUNA-N REINFORCED GID: BFBSXX

MANF: MOOG INDUSTRY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	14.39	9.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20307 FABRIC NYLON CHIFFON GID: BFBSXX

MANF: L TRAVIS TEXTILES
STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.003			00.53	NONE
C	1	023.8	014.5	0.003		00.94	12.00 T	NONE
B	1	025.9	014.3	0.004			09.70	NONE
C	2	025.9	014.3	0.005		00.58	12.00 T	NONE
C	1	025.9	014.3	0.005		03.04	12.00 T	NONE
A	1	030.0	009.0	0.030			05.00	NONE
A	1	030.0	009.0	0.004			02.60	NONE
C	2	100.0	020.2	0.004		04.50	12.00 T	NONE
C	1	100.0	020.2	0.004		03.30	12.00 T	NONE

FSC

RT	FLUID NAME
A	AMMONIA

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	1.37	.09		

ODOR

RT	RT WEIGHT	CURE
A	V 00001.58	

TOXICITY

69863 FABRIC NYLON CHIFFON A5652/4 GID: BFBSXX

MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	100.0	020.2	0.003		4.00	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-6	1.60	.10	1.08	

ODOR

RT	RT WEIGHT	CURE
A	V 5.12	

TOXICITY

20523 FABRIC NYLON DACRON COATED GID: BFCDXX

MANF: RICHARDSON CO SPEC: ST12D733-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.022			00.60	NONE
X	1	025.9	014.3	0.022		00.46	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.9E-7	.15	.02		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.39	

TOXICITY

60267 FABRIC NYLON FLAME RETARD GID: BFBSXX

MANF: SPEC: USB-MS-1009

....NO TEST DATA AVAILABLE....

80131 FABRIC NYLON M11480 POLYURETHANE COATED GID: EXXXXX

MANF: URETEK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	030.0	010.0	0.021			00.10	NONE
A	1	030.0	010.0	0.021			05.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	K 21.498	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005594 1

61062 FABRIC NYLON MESH 8885 GID: BFBVXX

MANF: FABLOCK MILLS SPEC: MIL-C-8061

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.042		00.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00020.40	

20895 FABRIC NYLON MESH NON-MELTING GID: BIBSXX

MANF: STERN & STERN SPEC: MB0135-060

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.009			00.10	NONE
C	1	020.9	014.7	0.009			05.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.4E-6	4.02	.06	2.57	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

69990 FABRIC NYLON POLYURETHANE COATED

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.011		00.10	12.00	T MOD
X	1	030.0	010.0	0.011		00.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.0E-6	1.74	.38	1.01	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	22.869	

20343 FABRIC NYLON RIPSTOP UNCOATED GID: BFCDXX

MANF: CHEMPRENE SPEC: ST11N593-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.009		01.17	12.00	T NONE
X	1	025.9	014.3	0.009		00.67	12.00	T MOD
I	1	030.0	009.0	0.008		01.22	01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	1.75	.28		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00034.33	

61160 FABRIC NYLON SILICONE COATED 1409 GID: DTCKBS

MANF: CONN HARD RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.2E-7	1.19	.15		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

20579 FABRIC NYLON URETHANE COATED GID: BFCQXX

MANF: INTERNATIONAL LATEX
KENYON PIECE DYEWORKS
URETEK

SPEC: ASTM E595-77 ST12N758-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.013		00.50	12.00	T MOD
X	2	025.9	014.3	0.010		00.17	12.00	T MOD
X	1	025.9	014.3	0.010		00.94	12.00	T MOD
X	2	030.0	010.0	0.012		0.10	12.00	T SMALL
X	1	030.0	010.0	0.012		0.70	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
[illegible]	[illegible]	[illegible]	[illegible]	[illegible]	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	21.029	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005595 3

20733 FABRIC NYLON URETHANE COATED 6611 GID: BFBVCQ

MANF: KENYON PIECE DYEWORKS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.010		00.68	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00014.60	

80165 FABRIC NYLON URETHANE-CARBON IMPREGNATED COATED GID: BGXXXX

MANF: REEVES BROS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.013			00.20	NONE
B	1	020.9	014.7	0.013		0.6	06.20	SMALL
I	1	030.0	010.0	0.013		0.9	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
V	21.501	

63861 FABRIC NYLON-OXFORD GID: EXXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00050.00	

62812 FABRIC NYLON/ACHESON +500 GID: BFBSXX

MANF: SPEC: MIL-C-12369F

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.035			09.00	MOD
X	1	020.9	014.7	0.035		00.75	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61013 FABRIC NYLON/COTTON RES JACKET GID: BFBSFS

MANF: ALICE KING CHATHAM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00072.21	

62813 FABRIC NYLON/DYNATHERM D65 GID: BFBSXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.043			07.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62915 FABRIC NYLON/FLUOROLUBE OIL GID: BFBSXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.025			05.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62916 FABRIC NYLON/KEL-F 90 GREASE GID: BFBSXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.060			04.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

01597 FABRIC NYLON/NEOPRENE COATED GID: BFBSDB

MANF: CHEMPRENE SPEC: ST12N735-01/ILC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.020			00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005596 5

01597 FABRIC NYLON/NEOPRENE COATED (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	025.9	014.3	0.020		00.59	12.00	T NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.68	1.20	.00	

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	A	00009.71	

61994 FABRIC NYLON/PVC HERCULITE 20 GID: BFBSAE

MANF: HERCULITE CORP SPEC: MIL-C-43006

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.014			05.00	NONE
C	1	023.8	014.5	0.014		00.85	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
	No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.8E-6	30.31	13.37		24H-150F-

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
	V	00010.51	24H-150F-

61298 FABRIC NYLON/PVC TXN266 GID: BFAEBS

MANF: COOLEY INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.026		00.53	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
	No test data						

62709 FABRIC NYLON/URETHANE 1111 COATED GID: BFBVCQ

MANF: URETEK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.010		00.75	12.00	T MOD

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
	No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
	A	00019.68	

80104 FABRIC NYLON/URETHANE 1414 COATED/ALUMINIZED AND URESEAL CEMENT GID: EXXXXX

MANF: URETEK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.010			04.30	MOD
X	2	030.0	010.0	0.100		00.20	12.00	SMALL
X	1	030.0	010.0	0.010		00.60	12.00	MOD

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
	No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
X

TOXICITY

RT	RT	WEIGHT	CURE
	A	21.297	

06421 FABRIC NYLON/VINYL RED 1024 GID: BFBVXX

MANF: SUN CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.015		00.03	12.00	T MOD
X	1	025.9	014.3	0.015		00.68	12.00	T MOD

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
	No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
	A	00019.94	

62917 FABRIC NYLON/VITON GID: BFBSXX

MANF: DIXIE CLAY SPEC: MIL-C-12369F
EH34

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005597 7

62917 FABRIC NYLON/VITON (cont)

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.038		00.00	00.00	NONE	No test data		No test data						
A	1	020.9	014.7	0.030			02.00	NONE									

62918 FABRIC NYLON/VITON/ACHESON+500 GID: BFBSXX
MANF: EH34

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.037			01.00	NONE	No test data		No test data						
X	1	020.9	014.7	0.050			04.50	MOD									
A	1	020.9	014.7	0.036		00.00	00.00	NONE									
A	1	020.9	014.7	0.040		00.00	00.00	NONE									

62919 FABRIC NYLON/VITON/FLUOREL GID: BFBSXX
MANF: EH34

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.030			03.50	NONE	No test data		No test data						
A	1	020.9	014.7	0.037			01.00	NONE									

20314 FABRIC ORTHO 116 GID: BFCNXX
MANF: FABRIC DEVELOPMENT SPEC: ST116041-01

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.021			03.10	NONE	A	AMMONIA	No test data						
A	1	025.8	014.3	0.025			02.40	NONE									
X	1	025.9	014.3	0.020			03.40	MOD									
A	1	030.0	009.0	0.024			03.30	NONE									
A	1	030.0	010.4	0.022			03.80	NONE									
X	1	033.0	014.3	0.020		00.08	08.90	MOD									
A	1	033.0	014.3	0.020			04.00	SMALL									
X	1	033.0	009.0	0.024		00.10	07.00	NONE									
X	1	033.2	015.5	0.019		00.18	12.00	T MOD									
B	1	035.0	014.3	0.019		00.14	06.90	SMALL									
X	1	040.0	014.3	0.020		00.22	12.00	T MOD									
I	1	040.0	009.0	0.019		00.14	12.00	T SMALL									
X	1	050.0	014.3	0.022		00.13	12.00	T MOD									
I	1	100.0	005.0	0.020		01.25	11.40	T NONE									

THERMAL VACUUM STABILITY				
RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.78	.03		

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	A	00029.70	

64032 FABRIC P101VIP GID: BFXXXX
MANF: ANTIFLASH CORP

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
I	1	025.9	014.3	0.020		00.40	12.00	T NONE	No test data		No test data						

63755 FABRIC P310 ULTRA GID: BFXXXX
MANF: ANTIFLASH CORP

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
I	1	025.9	014.3	0.010		00.50	12.00	T NONE	No test data		No test data						
I	1	030.0	010.0	0.010		00.60	12.00	T NONE									

MSFC-HDBK-527 REV F 9999942 0005598 9

Information Handling Services, 2000

63756 FABRIC P313 GID: BFXXXX
MANF: ANTIFLASH CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.020		00.30	12.00	T NONE
I	1	030.0	010.0	0.020		00.40	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62920 FABRIC PAN 2700-40 GID: BFXXXX
MANF: PRODESCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.055		00.40	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60615 FABRIC PANOTEX GRAY P-32 GID: BFBVXX
MANF: UNIVERSAL CARBON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.020			00.20	NONE
B	1	025.9	014.3	0.020			09.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.3E-6	6.72	.18	5.80	

ODOR

RT	RT WEIGHT	CURE
A	K 00020.18	

TOXICITY

05506 FABRIC PBI GID: BFHEXX
MANF: FABRIC RESEARCH LAB
SPEC: SE-T-0092

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.014			02.30	NONE
A	1	030.0	009.0	0.030			01.00	NONE
A	1	030.0	009.0	0.010			01.50	NONE
A	1	030.0	010.0	0.014			02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	10.18	.05	8.08	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06361 FABRIC PBI 73300-250 FX BRAID GID: BFHEGR
MANF: ALBANY INTERNATIONAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.080		00.00	00.00	NONE
A	1	030.0	009.0	0.030			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65208 FABRIC PBI 84410-426 BRAID GID: BMHEXX
MANF: ALBANY INTERNATIONAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.050		00.20	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61162 FABRIC PBI FRL-73300-131 GID: BFCDXX
MANF: FABRIC RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.013			02.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.4E-7	1.50	.09	.00	

ODOR

RT	RT WEIGHT	CURE
A	V 00010.99	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005599 0

60961 FABRIC PBI FRL-73300-190 FX GID: BFHEXX

MANF: FABRIC RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.012			01.50	NONE
A	1	025.9	014.3	0.012			01.40	NONE
A	1	025.9	014.3	0.019			01.10	NONE
A	1	030.0	009.0	0.012			01.00	NONE
A	1	030.0	009.0	0.019			01.10	NONE
I	1	033.0	009.0	0.012		00.01	12.20	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	9.0E-6	13.18	.00		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.65	

61008 FABRIC PBI FRL-73300-196 FX GID: BFXXXX

MANF: FABRIC RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.013			00.70	NONE
A	1	025.9	014.3	0.016			00.80	NONE
A	1	030.0	009.0	0.013			00.70	NONE
A	1	030.0	009.0	0.019			03.50	NONE
A	1	033.0	009.0	0.013			01.70	NONE
A	1	040.0	009.0	0.013			01.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00007.90	

61671 FABRIC PBI FRL-73300-197 GID: BF XX

MANF: FABRIC RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.019			00.50	NONE
A	1	030.0	009.0	0.019			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61670 FABRIC PBI FRL-73300-197 FX GID: BFHEXX

MANF: FABRIC RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.019			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61197 FABRIC PBI FRL-73300-201 FX GID: BFHEXX

MANF: FABRIC RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.019			01.00	NONE
A	1	030.0	009.0	0.019			01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20454 FABRIC PBI S-141 FX WEBBING GID: BMHEXX

MANF: FABRIC RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.067		00.00	00.00	NONE
A	1	030.0	009.0	0.067		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.2E-6	8.28	.03	6.74	24H-110F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00020.08	24H-110F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005600 3

05950 FABRIC PBI S-164 FX RASCHELNET GID: BFHEXX
MANF: FABRIC RESEARCH LAB
....NO TEST DATA AVAILABLE....

20767 FABRIC PBI S-165 FX GID: BFCBXX
MANF: FABRIC RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.017			01.40	NONE
A	1	025.9	014.3	0.039			00.50	NONE
A	1	030.0	009.0	0.039			00.50	NONE
A	1	033.0	009.0	0.017			01.20	NONE
A	1	040.0	009.0	0.017			01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.2E-6	7.47	.02		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00019.60	

20714 FABRIC PBI S-210 FX 4.80Z/SQYD GID: BFCDXX
MANF: FABRIC RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.017			00.70	NONE
A	1	030.0	009.0	0.017			00.70	NONE
X	1	100.0	020.2	0.017		00.27	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	10.91	.20		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.59	

20738 FABRIC PBI S111 FX WEBBING GID: BMHEXX
....NO TEST DATA AVAILABLE....

20739 FABRIC PBI S151 FX WEBBING GID: BMHEXX
....NO TEST DATA AVAILABLE....

63479 FABRIC PELLON #7015 GID: BFXXXX
MANF: PELLON CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	1.33	.02	.82	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

06229 FABRIC PELLON FR 954 GID: BFCBXX
MANF: PELLON CORP
SPEC: MA0105-330

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.068		00.17	12.00	T MOD
X	1	025.9	014.3	0.068		01.33	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	7.2E-7	8.91	.30		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00016.25	

60872 FABRIC PHENOLIC/CARBON FM5055G GID: BFFOBX
MANF: HITCO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.2E-7	2.91	.02		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005601 5

61148 FABRIC PHENOLIC/RESIN R1492Y12 GID: AZFLBX

MANF: RAYBESTOS-MANHATTAN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.40	.01		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60298 FABRIC PHENOLIC/SILICA GID: BFXXXX

MANF: SPEC: MIL-F-47018CC

....NO TEST DATA AVAILABLE....

05610 FABRIC POLYAMIDE TYPE ASI GID: BFCKAR

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.012			00.20	NONE
C	1	023.8	014.5	0.012		00.11	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.1E-7	.37	.16		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

03002 FABRIC POLYBENZIMIDAZOLE (PBI) GID: BFHEXX

MANF: CELANESE SPEC: MSW-309

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.030		00.00	00.00	NONE
A	1	030.0	009.0	0.010			01.50	NONE
A	1	030.0	009.0	0.030			00.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00020.42	

TOXICITY

60676 FABRIC POLYESTER E-1438 GID: BFCBXX

MANF: KENDALL SPEC: ST11D057

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.002		00.00	00.00	NONE
X	1	023.8	014.5	0.002			05.60	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.3E-6	.28	.00		

ODOR

RT	RT WEIGHT	CURE
A	X 00001.14	

TOXICITY

65336 FABRIC POLYESTER FILTER GID: BFXXXX

MANF: TETKO INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.8E-6	.24	.03	.11	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61975 FABRIC POLYESTER KK14 FR GID: BFCBXX

MANF: PELLON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.008			00.60	NONE
C	1	025.9	014.3	0.008		05.00	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00002.55	

TOXICITY

MSFC-HDBK-527 REV F 9999942 0005602 7

Information Handling Services, 2000

20594 FABRIC POLYESTER KNIT GID: BFCBXX

MANF: FABRIC DEVELOPMENT — SPEC: ST11P759-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.015			03.50	NONE
A	1	033.0	014.3	0.015			04.70	NONE
X	1	100.0	020.2	0.014		03.75	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-5	.53	.02		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00010.20	

20388 FABRIC POLYESTER NON-WOVEN GID: BFCBXX

MANF: KENDALL — SPEC: ST11D057-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.003			03.60	SMALL
C	1	025.9	014.3	0.003		01.69	11.00	T NONE
X	1	033.0	014.3	0.003		02.77	11.00	T MOD

FSC

RT	FLUID NAME
A	AMMONIA

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-7	.25	.02		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00000.78	

62921 FABRIC POLYESTER RF415 GID: BFCBXX

MANF: GOODYEAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5			00.30	08.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60617 FABRIC POLYESTER STYLE 15458 GID: BFCBXX

MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.005			00.70	NONE
X	1	025.9	014.3	0.005		01.12	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.34	

60982 FABRIC POLYESTER STYLE67004/08 GID: BFCBXX

MANF: BURLINGTON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.007			09.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00009.78	

20759 FABRIC POLYESTER URETHANE COATED GID: BFCQCB

MANF: URETEK — SPEC: ST12B771-01/ILC ST12B771-02/ILC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.015		00.09	12.00	T MOD
X	1	025.9	014.3	0.015		00.47	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.4E-5	1.10	.23		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.07	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005603 9

20761 FABRIC POLYESTER/COTTON GID: BFFSXX
MANF: ALPHA MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.020		00.10	12.00	T SMALL
C	1	025.9	014.3	0.020		01.43	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.56	

06404 FABRIC POLYESTER/PVS L-109 KUP
MANF: COOLEY INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.012			02.20	NONE
X	1	025.9	014.3	0.012		00.78	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.19	

61633 FABRIC POLYETHER POLYURETHANE COATED NYLON GID: BFCQBV
MANF: URETEK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.007		00.14	12.00	T MOD
X	1	025.9	014.3	0.007		00.59	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.46	

65357 FABRIC POLYGUARD II GID: BFXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00022.67	

61884 FABRIC POLYIMIDE FIBER GID: BFCDXX
MANF: FABRIC RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.058		00.15	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00015.29	

65130 FABRIC POLYPRO LYCRAL/POLYES GID: BFCBXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.030		00.80	12.00	T MOD-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00022.98	FLEXITHERM

06636 FABRIC POLYPROPYLENE 3X5WHDC GID: BFCGXX
MANF: AIRCRAFT POROUS MEDIA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.060			00.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005604 0

06636 FABRIC POLYPROPYLENE 3X5WHDC (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.060			07.40	MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	K 00019.66	

20920 FABRIC POLYPROPYLENE 4X5 WHDC GID: BFXXXX

MANF: AIRCRAFT POROUS MEDIA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.026				SMALL
B	1	030.0	010.0	0.026		00.70		SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	K 00021.13	

20303 FABRIC POPLIN COTTON AND DACRON GID: BFXXXX

MANF: BURLINGTON

....NO TEST DATA AVAILABLE....

61015 FABRIC POPLIN NOMEX GID: BFBVCQ

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.4	0.012		00.75	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80175 FABRIC PYROMEX A-201 GID: BFXXXX

MANF: TOHO RAYON CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.020			05.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 21.402	

63480 FABRIC QUARTZ GID: BFXXXX

MANF: SPEC: HMS 20-1654

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.265		07.10	07.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.09	.01	.03	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

62457 FABRIC RAYON GOAT HAIR GID: BFGOXX

MANF: STACY FABRICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.037		00.76	09.70 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 00056.76	

60952 FABRIC RAYON/NOMEX GID: BFGRXX

MANF: AVTEX FIBERS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005605 2

60953 FABRIC RAYON/WOOL GID: BFGRXX
MANF: AVTEX FIBERS

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	025.9	014.3	0.012		01.44	12.00	T NONE	No test data		No test data							

61163 FABRIC RCF 328-1C GID: BFIACK
MANF: RUBBER CTD FABRICS

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.033			02.10	SMALL	No test data		No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	3.2E-7	.74	.54		

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

00495 FABRIC REFRASIL C100-48 SILICA GID: BFXXXX

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.02	.02	.00	

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

05024 FABRIC REFRASIL C1554-48 IRISH GID: BFXXXX
....NO TEST DATA AVAILABLE....

62922 FABRIC RIPSTOCK NYLON/VINYL COATED GID: BFCVBS

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.020			05.00	SMALL	No test data		No test data							

64464 FABRIC RTV E 1581 GLASS GID: BFIAXX
MANF: QPL SPEC: MIL-C-9084T8
ROCKETDYNE

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.040			00.30	SMALL	No test data		No test data							
X	1	030.0	009.0	0.155		00.06	12.00	T LARGE										

60940 FABRIC RYTON GID: BFCHXX
MANF: ALBANY INTERNATIONAL

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.010			00.20	NONE	No test data		No test data							
X	1	025.9	014.3	0.010			07.30	MOD										
S	2	025.9	014.3	0.012			00.30	NONE										
S	1	025.9	014.3	0.012			05.50	NONE										
S	1	025.9	014.3	0.011			04.60	NONE										
I	1	030.0	009.0	0.011		00.33	12.00	T SMALL										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.36	.06	.08	

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
K	00020.23		

20409 FABRIC SATEEN COTTON 40Z/YD GID: BFFSXX
MANF: COTTON INC

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	2	025.9	014.3	0.013			00.20	NONE	No test data		No test data							
B	1	025.9	014.3	0.013			08.50	NONE										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
A	K 00008.49		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005606 4

61023 FABRIC SATEEN EX 1B NC 6.9 OZ GID: BFFSGR

MANF: COTTON INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.015			04.50	NONE
B	1	030.0	010.4	0.015			07.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.33	

63515 FABRIC SHIRT GID: BFXXXX

MANF: PATAGONIA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.018		00.06	06.30	NONE
X	1	025.9	014.3	0.017		00.67	12.00	T MOD
X	1	025.9	014.3	0.030		18.00	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20613 FABRIC SHIRT JOE NAMATH GID: BFFSCB

MANF: ARROW SHIRT CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.018		00.25	12.00	T MOD
X	1	025.9	014.3	0.018		02.40	12.00	T MOD
X	1	033.0	014.3	0.018		03.00	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00007.15	

20615 FABRIC SHORTS BOXER GID: BFCBFS

MANF: JOCKEY INTERNATIONAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.008		01.82	14.40	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00063.31	

20617 FABRIC SHORTS JOCKEY GID: BFFSXX

MANF: JOCKEY INTERNATIONAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.010		00.87	14.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00055.28	

61835 FABRIC SILICA C1154-48 GID: BFHKXX

MANF: HITCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.90	.02		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005607 6

62923 FABRIC SILICONE 1 GLASS GID: BFDPGD
MANF: CONN HARD RUBBER SPEC: AMS 3320

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	024.5	014.5	0.018		00.84	10.60	NONE	No test data	No test data							

06515 FABRIC SILICONE 7243G1523 GID: BFCKFV
MANF: ARROWHEAD PRODUCTS

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.030			00.70	NONE	No test data	No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	.81	.29	.01	

ODOR			TOXICITY
RT	RT WEIGHT	CURE	
No test data			

61290 FABRIC SILICONE RUBBER/ARAMID GID: BBDPJH
MANF: QSL/MOHAWK MILLS SPEC: MB0135-055 ZZ-R-765

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7	0.060			08.50	SMALL	No test data	No test data							

61571 FABRIC SILICONE/ARAMID7311NHT6 GID: BFCKJH
MANF: ARROWHEAD PRODUCTS

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.024			02.60	SMALL	No test data	No test data							
I	1	020.9	014.7	0.011		00.22	11.20	T SMALL									

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	2.7E-6	.68	.00		8H-400F-

ODOR			TOXICITY
RT	RT WEIGHT	CURE	
No test data			

61866 FABRIC SILICONE/ARMID 7311K120 GID: BFCKJH
MANF: ARROWHEAD PRODUCTS

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.047			04.00	SMALL	No test data	No test data							
I	1	020.9	014.7	0.012		00.17	11.90	T NONE									

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	3.2E-6	.52	.06		8H-400F-
					24H-70F-

ODOR			TOXICITY
RT	RT WEIGHT	CURE	
No test data			

06221 FABRIC SILICONE/CR/PTFE V3037 GID: BFCKXX
MANF: SPEC: MB0135-028
....NO TEST DATA AVAILABLE....

64443 FABRIC SILICONE/GLASS GID: BFCKIA
MANF: UMPCO SPEC: SK85052-3

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.050			02.90	NONE	No test data	No test data							

61996 FABRIC SILICONE/GLASS 3010 GID: BFCKIA
MANF: CONN HARD RUBBER SPEC: AMS 3315

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	023.8	014.5	0.010		00.18	12.00	T SMALL	No test data	No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005608 8

61996 FABRIC SILICONE/GLASS 3010 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.0E-6	.04	.00		16H-480F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

61527 FABRIC SILICONE/GLASS 3016 GID: BFCKIA

MANF: CONN HARD RUBBER

SPEC: AMS 3315C

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.015			02.70	NONE
I	1	023.8	014.5	0.015		00.17	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61423 FABRIC SILICONE/GLASS GS200 GID: FBXXXX

MANF: BESTOBELL AVIATION
ESA/ERNO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.080			00.50	NONE
A	1	025.9	014.3	0.080			00.50	NONE
A	1	030.0	009.0	0.055			02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64985 FABRIC SILICONE/GLASS SG1M GID: BFXXXX

....NO TEST DATA AVAILABLE....

61171 FABRIC SILICONE/GLASS WITH ZIPPER GID: EEDPXX

MANF: ZIPPERTUBING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.149			10.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60295 FABRIC SILICONE/NYLON H565 GID: BFCKBS

MANF: AIRCRAFT PRODUCTS

SPEC: ZZ-R-765 CL 3B GR 50

....NO TEST DATA AVAILABLE....

61874 FABRIC SPACER 6027-1-1 GID: BOXXXX

MANF: UNIROYAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.194		00.13	12.00	T MOD
X	1	023.8	014.5	0.194		00.57	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.7E-6	1.35	.42		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00018.16	

20659 FABRIC SPANDEX 90221/FIN 1635 GID: BFCQXX

MANF: LIBERTY FABRICS INC

SPEC: ST11N1018-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.018		01.08	11.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	2.53	.61		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.73	

20301 FABRIC SPANDEX NYLON GID: BFCSXX

MANF: DARLINGTON FABRICS

SPEC: ST11N117-04

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.021		00.12	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005609 T

DATE: 12/23/88
NON-METALS BY DESIGNATION

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

20301 FABRIC SPANDEX NYLON (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.021		00.61	12.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	6.0E-6	2.88	.60		

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00009.77	

65401 FABRIC SPECTRA 900 GID: BFGDXX
MANF: ALLIED FIBERS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.020		01.10	12.00	T NONE

THERMAL VACUUM STABILITY

No test data

FSC

No test data

OXYGEN COMP

No test data

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00021.08	

06375 FABRIC SRGA 0213 ALUM/GLAS/SIL GID: BBIACK
MANF: 3M CO
....NO TEST DATA AVAILABLE....

80259 FABRIC STILAN 541 WOVEN GID: BFXXXX
MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.012		0.1	12.00	T NONE

FSC

No test data

OXYGEN COMP

No test data

80218 FABRIC STRAP CONTAINER COVER ND-3010 C/#1 GID: BFXXXX
MANF: TEIKOKU SEN-I CO

THERMAL VACUUM STABILITY

No test data

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	18.026	

60671 FABRIC STYLE 5035 FINISH 8362 GID: BFXXXX
MANF: J P STEVENS
....NO TEST DATA AVAILABLE....

80111 FABRIC SUNBRELLA FIRESIST 8601 ARTIC BLUE GID: BFXXXX
MANF: GLEN RAVEN MILLS
SPEC: NFPA 701

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7			00.20	06.25	NONE
I	1	024.5	014.5			0.35	12.00	T NONE
I	1	025.9	014.3			00.30	12.00	T NONE

THERMAL VACUUM STABILITY

No test data

FSC

No test data

OXYGEN COMP

No test data

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	18.4	

61046 FABRIC SUPERTWILL 48 COTTON GID: BFFSXX
MANF: MCCAMPBELL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.012		01.05	12.00	T NONE

FSC

No test data

OXYGEN COMP

No test data

20299 FABRIC T162-42 GID: BFCNXX
MANF: STERN & STERN
SPEC: ST11T391-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.008			02.20	NONE

FSC

RT	FLUID NAME
A	AMMONIA

OXYGEN COMP

No test data

MSFC-HDBK-527 REV F 9999942 0005610 6

Information Handling Services, 2000

20299 FABRIC T162-42 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	033.0	014.3	0.008			03.90	NONE
X	1	100.0	006.0	0.008		00.24	12.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.03	.00		

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00018.96	

05476 FABRIC TACONIC 7159-128 TEFLON GID: BFCNGD

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.015			00.10	NONE
A	1	023.8	014.5	0.015			01.10	NONE
A	1	030.0	009.0	0.012			02.00	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.6E-6	.01	.00		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

69849 FABRIC TECKNIT 72-00008 FLEX CONDUCTIVE EPOXY S.F.

MANF: TECKNIT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	1.02	.11	.24	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

69859 FABRIC TECKNIT 72-00014

MANF: TECKNIT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	100.0	011.1	0.016	0.003	0.10	12.00	T NONE
A	1	100.0	004.4	0.011	0.003		01.80	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE

65423 FABRIC TECKNIT 72-08116AG FILL GID: BFXXXX

SPEC: MIL-A-47089

MANF: TECKNIT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	100.0	004.4	0.010	0.003	00.80	12.00	T SMALL
I	1	100.0	011.0	0.010	0.003	01.70	12.00	T SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.61	.03	.00	.5H-210F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00018.20	

61052 FABRIC TECKNIT 77-09-776 GID: BFXXXX

MANF: TECKNIT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.009		01.20	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20616 FABRIC TEE SHIRT GID: BFRSCB

MANF: BEN HOGAN
JOCKEY INTERNATIONAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
Y	1	023.8	014.5	0.009		02.61	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005611 8

20616 FABRIC TEE SHIRT (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.014		02.85	12.00	T NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	A	00247.69	

60162 FABRIC TEFLON GID: BFCNXX
MANF: STERN & STERN SPEC: EI 4164

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.016			03.70	SMALL
A	1	030.0	009.0	0.016			03.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
	K	00020.36	

61121 FABRIC TEFLON 30 GID: BFCNXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	500		250	0.006	0	20
B	MECH	500	72	250	0.006	0	05
B	PNEU	500		70	0.006	0	20
B	MECH	500	72	70	0.006	0	20

20340 FABRIC TEFLON T-83-54 GID: BFCNXX
MANF: STERN & STERN SPEC: ST12T168-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005			03.30	NONE
A	1	025.9	014.3	0.012			00.90	NONE
A	1	033.0	014.3	0.012			02.40	NONE
X	2	100.0	020.2	0.012			02.30	NONE
X	1	100.0	020.2	0.012		01.09	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-7	.21	.02		

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
	A	00010.35	

60957 FABRIC TEFLON T162 GID: BFCNXX
MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	033.0	009.0	0.010			03.70	SMALL
A	1	040.0	009.0	0.010			04.70	SMALL

FSC

RT	FLUID NAME
A	HYZE
A	MMH
C	MMH
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20376 FABRIC TEFLON T21-42 GID: BFCNXX
MANF: STERN & STERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.018			00.10	NONE
B	1	025.9	014.3	0.018			09.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.28	.00		

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
	A	00038.43	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005612 T

61555 FABRIC TEFLON T9362/TFE COATED GID: BFCNHS
MANF: PRODESCO SPEC: MB0135-027F

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.009			01.40	NONE	No test data		No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.2E-6	.02	.02	.00	

ODOR			TOXICITY	
RT	RT WEIGHT	CURE		
No test data				

63923 FABRIC TEFLON/COATED BETA CLOTH GID: BFCOHL
MANF: OAK INDUSTRIES SPEC: MB0135-027FMGF MB0135-027GF

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.03	.01	.00	

ODOR			TOXICITY	
RT	RT WEIGHT	CURE		
No test data				

00573 FABRIC TFE GLASS TG 4060 GID: BFCPXX
MANF: CHEMICAL FABRICS

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	030.0	009.0	0.006			01.60	NONE	No test data		X	PNEU	1000		275	0.006	3	17
											B	MECH	14.7	10	-297	0.006	0	20
											C	MECH	200	55	200	0.006	0	20
											B	PNEU	400		275	0.006	0	63
											B	PNEU	400		70	0.006	0	20
											X	PNEU	500		275	0.006	02	20
											C	MECH	600	72	250	0.090	02	20
											B	MECH	600	72	72	0.090	0	20

85523 FABRIC THERMOGLASS HEAT TREATED
MANF: AMATEX SPEC: MIL-C-20079G YARN
....NO TEST DATA AVAILABLE....

61679 FABRIC TREVIRA POLYEST 203 GRN GID: BFCBXX
MANF: HOECHST FIBERS

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	030.0	010.4	0.011			01.10	12.00 T MOD	No test data		No test data							

60894 FABRIC TREVIRA POLYEST 207 GRN GID: BFCBXX
MANF: HOECHST FIBERS

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	030.0	010.4	0.013			00.90	12.00 T MOD	No test data		No test data							

61873 FABRIC TREVIRA POLYESTER 271 GID: BFCBXX
MANF: HOECHST FIBERS

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	023.8	014.5	0.020			06.90	SMALL	No test data		No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	3.8E-6	.23	.05		60H-70F-

ODOR			TOXICITY	
RT	RT WEIGHT	CURE		
A	A 00011.27			

61022 FABRIC TWILL EX 3A 1.93 6.9 OZ GID: BFFSGR
MANF: COTTON INC

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	025.9	014.3	0.015			07.40	NONE	No test data		No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005613 1

63763 FABRIC TYVEK 1442 GID: BFCEXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.012		00.32	02.70	NONE
B	1	024.5	014.5	0.009			07.80	NONE
I	1	030.0	010.0	0.009		01.60	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00021.77	

63980 FABRIC UNITIKA 1 GID: BFXXXX
MANF: UNITIKA CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.020		00.900	12.00 T	NONE
I	1	030.0	010.0			00.900	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20331 FABRIC UTOPIA STYLE #540982 GID: BFCBFS
MANF: BURLINGTON SPEC: ST11D126-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.011		00.09	12.00 T	NONE
X	1	025.9	014.3	0.011		01.16	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	9.0E-7	1.70	.03		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00005.06	

06433 FABRIC VD0001 DACRON/VITON GID: BFCBDE
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.009			00.20	NONE
X	1	025.9	014.3	0.009		00.54	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.65	

20462 FABRIC VELVETEEN GID: BFFSXX
MANF: CROMPTON HIGHLANDS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.045		00.07	12.00 T	NONE
C	1	025.9	014.3	0.045		01.24	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.2E-7	3.76	.00		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00201.30	

63114 FABRIC VINYL/NYLON LAMIN NOC GID: BGBSCU

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7				05.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64031 FABRIC VIP INTERLOCK KNIT GID: BFXXXX
MANF: ANTIFLASH CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.020		00.50	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005614 3

61768 FABRIC WOOL FLOVAN TREATED GID: BFGZXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.038		00.60	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00021.77	

06074 FABRIC X-389-7 BETA/GLASS/TFE GID: BFHLCN

MANF: DODGE SPEC: MB0135-027

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.008			01.00	SMALL
A	1	030.0	009.0	0.009			00.90	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.03	.01	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00094.95	

69902 FABRIC X-OGEN CAVALRY TWILL LAVANDER 85% WOOL/15% KEVLAR GID: BFXXXX

MANF: ANTON MAIX FABRICS INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.050		0.50	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

69844 FABRIC X-OGEN WOOL CORD #20 PETROL 80% WORSTED WOOL 20% KEVLAR CARBON GID: BFXXXX

MANF: ANTON MAIX FABRICS INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.060		0.050	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62548 FABRIC ZIRCONIUM TREATED WOOL GID: BFGZAE

MANF: INTERCEL
LANGENTHAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.065		00.50	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00028.60	

06213 FABRIC/TAPE 581 QUARTZ (INORGANIC) GID: BFXXXX

MANF: J P STEVENS SPEC: MB0135-071

....NO TEST DATA AVAILABLE....

65534 FABRICOAT SRGA-0209 GID: AKXXXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	23.60	

60400 FABROID T1 GLASS/TEFLON 50/50

MANF: LEAR SIEGLER

....NO TEST DATA AVAILABLE....

06024 FABULON GID: BPXXXX

MANF: SANGRAY CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00015.13	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005615 5

85473 FARBIC BALLASTIC NYLON COATED WITH NICKEL
MANF: VAPOR FAB INC

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7	0.028		00.04	09.50	T LARGE	No test data		No test data						

85406 FASTENER APLIX 810 POLYESTER HOOK GID: BOXXXX
MANF: APLIX SPEC: MIL-F-21840T2C3

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7	0.065		00.17	04.50	LARGE	No test data		No test data						

85405 FASTENER APLIX 810 POLYESTER LOOP GID: BOXXXX
MANF: APLIX SPEC: MIL-F-21840T2C3

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	20.9	14.7	0.100		00.20	12.00	LARGE	No test data		No test data						

85402 FASTENER APLIX 820 NOMEX NON-MELTING HOOK GID: BOXXXX
MANF: APLIX SPEC: MIL-F-21840T1C2

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
B	1	20.9	14.37	0.065		00.21	11.0	NONE	No test data		No test data						
I	1	25.9	14.3	0.065		00.27	12.0	T NONE									

85404 FASTENER APLIX 820 NOMEX NON-MELTING HOOK AND LOOP GID: BOXXXX
MANF: APLIX SPEC: MIL-F-21840T1C2

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.125		00.10	02.50	NONE	No test data		No test data						
I	1	25.9	14.3	0.100		00.17	12.0	T NONE									
I	1	25.9	14.3	0.125		00.12	12.0	T NONE									

85403 FASTENER APLIX 820 NOMEX NON-MELTING LOOP GID: COXXXX
MANF: APLIX SPEC: MIL-F-21840T1C2

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	20.9	14.7	0.100		00.10	03.00	NONE	No test data		No test data						

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	19.54	

63921 FASTENER DENISON GID: BNXXXX
MANF: DENNISON MFG

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	1.0E-6	2.71	.05	.00		No test data			

64122 FASTENER HL410V
MANF: HI LOK

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
S	5.0E-5					No test data			

62469 FASTENER KYNAR MK 7201 GID: BNCTXX
MANF: KAYNAR CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	9.0E-7	.00	.00				A	00020.24	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005616 7

62463 FASTENER PLASTIC BOOK BINDER GID: DKXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.026			00.10	NONE
X	1	025.9	014.3	0.026		00.24	10.80	T MOD
X	2	033.0	014.3	0.020			02.90	MOD
X	1	033.0	014.3	0.020		00.41	09.20	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00021.43	

63915 FASTENER POLYESTER SLIDE 321 GID: BNCBXX

MANF: AMERICAN ROBIN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.075		00.13	12.00	T NONE
X	1	025.9	014.3	0.075		00.40	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.5E-6	.28	.07	.04	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00022.67	

65492 FASTENER SCOTCHMATE DUAL LOCKING TY 400 GID: BNXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.140	0.003	00.10	11.30	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00022.64	

69954 FASTENER SCOTCHMATE HOOK SJ3419FR BLACK/ON BLACK NOMEX DUCK

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.106		00.10	12.00	T SMALL
X	1	030.0	010.0	0.108		00.30	11.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE
A	13.421	

80136 FASTENER SCOTCHMATE LOOP SJ3418FR ON BLACK NOMEX DUCK 7.5 OZ GID: BNBSBV

MANF: 3M CO/SOUTHERN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	030.0	010.0	0.139			00.30	NONE
B	1	030.0	010.0	0.145		0.28	09.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	28.40	

64931 FASTENER SCOTCHMATE SJ3400 HOOK GID: BOBSXX

MANF: 3M CO

....NO TEST DATA AVAILABLE....

64932 FASTENER SCOTCHMATE SJ3401 LOOP GID: BOBSXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
[illegible]					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005617 9

64933 FASTENER SCOTCHMATE SJ3402 HOOK GID: BOBSXX
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.72	.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64938 FASTENER SCOTCHMATE SJ3415 HOOK HS GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64943 FASTENER SCOTCHMATE SJ3418 LOOP FIRE/PR GID: BOBSXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.100		00.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00014.28	

TOXICITY

64944 FASTENER SCOTCHMATE SJ3419 HOOK FIRE/PR GID: BOBSXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.007		00.30	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00012.78	

TOXICITY

64957 FASTENER SCOTCHMATE SJ3441 TY 400 GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64958 FASTENER SCOTCHMATE SJ3442 TY 170 GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64951 FASTENER SCOTCHMATE SJ3501 SOL/HA ADHESIVE GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64952 FASTENER SCOTCHMATE SJ3502 SOL/HA ADHESIVE GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64936 FASTENER SCOTCHMATE SJ3503 PS ADHESIVE BACK GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64937 FASTENER SCOTCHMATE SJ3504 PS ADHESIVE BACK GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64934 FASTENER SCOTCHMATE SJ3509 HA ADHESIVE BACK GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005618 0

64939 FASTENER SCOTCHMATE SJ3511 HS ADHESIVE BACK GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64935 FASTENER SCOTCHMATE SJ3514 HA ADHESIVE BACK GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64945 FASTENER SCOTCHMATE SJ3526 HOOK/26 SER GID: BOBSXX
MANF: 3M CO

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	5.60	2.22	.00		No test data		

64946 FASTENER SCOTCHMATE SJ3527 LOOP/26 SER GID: BOBSXX
MANF: 3M CO

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	5.60	2.22	.00		No test data		

64947 FASTENER SCOTCHMATE SJ3528 HOOK/26 SER GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64948 FASTENER SCOTCHMATE SJ3530 HOOK/36 SER GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64949 FASTENER SCOTCHMATE SJ3537 LOOP/36 SER GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64950 FASTENER SCOTCHMATE SJ3538 HOOK/36 SER GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64959 FASTENER SCOTCHMATE SJ3541 TY 400 GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64960 FASTENER SCOTCHMATE SJ3542 TY 170 GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64955 FASTENER SCOTCHMATE SJ3551 TY 400 PS GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64956 FASTENER SCOTCHMATE SJ3552 TY 170 PS GID: BOBSXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

64953 FASTENER SCOTCHMATE SJ3571 LOOP PS ADHESIVE GID: BOBSXX
MANF: 3M CO SPEC: MIL-F-21840
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005619 2

64954 FASTENER SCOTCHMATE SJ3572 HOOK PS ADHESIVE GID: BOBSXX
MANF: 3M CO SPEC: MIL-F-21840
....NO TEST DATA AVAILABLE....

60973 FASTENER VECRO HI-AIR NYLON HOOK 65 WITH NOMEX GROUND GID: BOBVXX
MANF: VELCRO CORP SPEC: MIL-F-21840

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.056			04.30	NONE
X	1	025.9	014.3	0.070		00.61	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.33	2.05	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.10	

80318 FASTENER VELCOIN ON VINYL DISK/NYLON HOOK PS 0107

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.125	0.003		03.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00007.61	

20664 FASTENER VELCRO ADHESIVE 45 GID: BNXXXX
MANF: VELCRO CORP SPEC: ST30V983-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.3	0.006	0.003		02.90	NONE
A	1	023.8	014.3	0.006	0.003		02.90	NONE
A	1	024.5	014.3	0.006	0.003		02.90	NONE
A	1	025.9	014.3	0.006	0.003		02.90	NONE
A	1	030.0	014.3	0.004	0.003		04.00	NONE
A	1	033.0	014.3	0.004	0.003		04.00	NONE
X	1	100.0	020.2	0.006	0.003	03.27	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	7.07	.75		168H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00020.02	168H-70F- 24H-150F-

65422 FASTENER VELCRO ALL NON MELTING ARAMID LOOP 2000 GID: BOXXXX
MANF: VELCRO CORP SPEC: MIL-F-21840C2

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	4.40	1.07	2.07	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

63276 FASTENER VELCRO ARAMID HOOK 65 AND LOOP GID: BOXXXX
MANF: VELCRO CORP SPEC: MIL-F-218040ET1C2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.185			03.00	MOD
I	1	024.5	014.5	0.125		00.16	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64149 FASTENER VELCRO ASTRO HOOK 80 BACKING PS 3072 GID: BFCBXX
MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.090	0.003		00.40	NONE
C	1	030.0	010.0	0.090	0.003	00.09	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005620 9

64149 FASTENER VELCRO ASTRO HOOK 80 BACKING PS 3072 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00023.60	

63556 FASTENER VELCRO ASTRO HOOK AND LOOP GID: EXXXXX

MANF: PN100-004-233-3099AF
PN100-082-233-3099AF
VELCRO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00137.10	

64150 FASTENER VELCRO ASTRO LOOP 200 PS 3072 GID: BFCBXX

MANF: VELCRO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00022.70	

62219 FASTENER VELCRO ASTRO LOOP 634 WITH BETA GLASS GROUND GID: BNBVXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.117			02.70	NONE
A	1	033.0	014.3	0.117			03.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	5.0E-6	.72	.20		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.65	

63275 FASTENER VELCRO HAQ 12-2 HOOK AND LOOP BACKING RUBBER SILICONE GID: BODOXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.187			00.80	NONE
A	1	030.0	009.0	0.187			02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62800 FASTENER VELCRO HI-AIR HOOK 65 WITH PS 0372 GID: BOXXXX

MANF: VELCRO CORP

SPEC: EH32 (84-147)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	0.083		00.10	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00024.70	

63277 FASTENER VELCRO HI-AIR NOMEX HOOK 65 AND LOOP 2000 GID: BFBSXX

MANF: VELCRO CORP

SPEC: EH32 (83-288)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	0.125		00.08	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00022.50	

61657 FASTENER VELCRO HI-MEG NYLON LOOP IMPREGNATED WITH SILVER GID: BOBVXX

MANF: VELCRO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.1E-6	1.80	.10	1.50	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005621 0

60464 FASTENER VELCRO HOOK 80 BACKING 0399 GID: BFCBXX
MANF: VELCRO CORP

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	0.070		00.44	12.00	T MOD	No test data		No test data							

60465 FASTENER VELCRO HOOK 80 BACKING 1299 GID: BFCBXX
MANF: VELCRO CORP

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	0.075		00.68	12.00	T MOD	No test data		No test data							

60460 FASTENER VELCRO HOOK 80 BACKING 2699 GID: BFCBXX
MANF: VELCRO CORP

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	0.075		00.41	12.00	T MOD	No test data		No test data							

60459 FASTENER VELCRO HOOK 80 BACKING 2899 GID: BFCBXX
MANF: VELCRO CORP

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	0.075			05.00	MOD	No test data		No test data							

60461 FASTENER VELCRO HOOK 80 BACKING 9999 GID: BFCBXX
MANF: VELCRO CORP

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	0.070			06.00	MOD	No test data		No test data							

61909 FASTENER VELCRO HOOK 80 LOOP 2000 GID: BOCBXX
MANF: VELCRO CORP SPEC: SPARMAT 03:37

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	023.8	014.5	0.100		00.14	12.00	T MOD	No test data		No test data							
X	1	023.8	014.5	0.100		00.22	12.00	T MOD										

63269 FASTENER VELCRO HOOK 80 PS 3072 GID: BOXXXX
MANF: VELCRO CORP

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	024.5	014.5	0.085		00.85	12.00	T NONE	No test data		No test data							

60469 FASTENER VELCRO HOOK AND LOOP 100 BACKING 3099AB GID: BMCBXX
MANF: VELCRO CORP SPEC: P/N 100-004-233-3099AB P/N 100-082-233-3099AB

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.130			02.00	NONE	No test data		No test data							
A	1	030.0	009.0	0.130			01.90	NONE										

THERMAL VACUUM STABILITY						ODOR		TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE	
A	1.0E-6	.27	.02	.00		No test data			

62325 FASTENER VELCRO HOOK AND LOOP 1000 BACKING 0399 GID: BOBVXX
MANF: VELCRO CORP SPEC: P/N 1000-004-233-3099 P/N 1000-082-233-3099

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	030.0	010.4	0.092		00.19	12.00	T MOD	No test data		No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005622 2

62325 FASTENER VELCRO HOOK AND LOOP 1000 BACKING 0399 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.73	

62093 FASTENER VELCRO HOOK SJ3572 AND LOOP SJ3571 GID: BFBSXX

MANF: VELCRO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.7E-6	1.71	.08	.87	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

64145 FASTENER VELCRO KNIT NYLON LOOP 3005 BACKING 0699 GID: DYBSXX

MANF: VELCRO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.2E-6	2.31	.16	.96	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00022.33	

64153 FASTENER VELCRO LOOP 2000 BACKING 0100AB GID: BOXXXX

MANF: VELCRO CORP

SPEC: P/N 2000-001-012-0100AB

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00026.52	

60929 FASTENER VELCRO LOOP NYLON 80 WITH PS 0172 GID: BOBSAK

MANF: HARTWELL CORP
VELCRO CORP

SPEC: MIL-F-21840T2C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.130	0.010		04.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.09	

05073 FASTENER VELCRO MID-TEMP NYLON HOOK AND LOOP GID: DYBYXX

MANF: VELCRO CORP

SPEC: MIL-F-21840

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.111			10.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60879 FASTENER VELCRO NOMEX HAQ 12-1 HOOK WITH 6-1015 NEOPRENE ADHESIVE

MANF: VELCRO CORP

SPEC: MB0120-025 ADHESIVE MB0120-028 PRIMER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.100	0.020	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05547 FASTENER VELCRO NOMEX HAQ 12-1-200 NYLON HOOK GID: BOBVXX

MANF: VELCRO CORP

SPEC: MIL-C-38351T2C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.105		00.18	12.00 T	NONE
C	2	030.0	010.0	0.070			01.60	SMALL
C	1	030.0	010.0	0.070		00.10	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60758 FASTENER VELCRO NOMEX HAQ 12-2 LOOP WITH 6-1015 NEOPRENE ADHESIVE GID: BOBVDB

MANF: HARTWELL CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.105	0.020	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005623 4

05658 FASTENER VELCRO NOMEX HAQ 12-2-200 NYLON LOOP GID: BNBVXX
MANF: VELCRO CORP SPEC: MIL-C-38351T1C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.130			01.90	NONE
C	2	025.9	014.3	0.110	0.010		00.20	NONE
C	1	025.9	014.3	0.110	0.010	00.17	12.00	T SMALL
A	1	030.0	009.0	0.115	0.010		02.50	NONE
C	2	030.0	014.3	0.110	0.010		00.20	NONE
C	1	030.0	014.3	0.110	0.010	00.17	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.16	

62100 FASTENER VELCRO NOMEX HI-AIR HAQ 12-1 HOOK AND HAQ 12-2 LOOP GID: BOBVXX
MANF: VELCRO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.6E-6	5.36	1.64		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

61992 FASTENER VELCRO NOMEX HI-AIR HAQ 12-2-200-SAI LOOP AND 12-1-200 HOOK GID: BOBVXX
MANF: HARTWELL CORP
VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.124			05.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.1E-6	5.23	1.43		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00010.08	

60972 FASTENER VELCRO NOMEX HI-AIR LOOP 2000 BACKING 0199W GID: BOBVXX
MANF: VELCRO CORP SPEC: MIL-F-21840C4 P/N 1000-003-117-0199W

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.105		00.49	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.28	.00	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.36	

64148 FASTENER VELCRO NOMEX HI-AIR LOOP 2000 PS 0372 GID: BFCBXX
MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.125			04.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00022.01	

61185 FASTENER VELCRO NOMEX HOOK 0.75 INCH GID: BOBVXX
MANF: VELCRO CORP SPEC: ST17N080-01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	1.74	.06		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

65035 FASTENER VELCRO NOMEX HOOK 66 BACKING 0372 GID: BOBVXX
MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.090	0.003	00.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005624 6

60775 FASTENER VELCRO NOMEX LOOP 0.75 INCH GID: BOBVXX
MANF: VELCRO CORP SPEC: ST17N080-02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.1E-6	1.53	.04		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61188 FASTENER VELCRO NOMEX LOOP 1 INCH GID: BOBVXX
MANF: VELCRO CORP SPEC: ST13L818-07

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.1E-6	1.87	.03		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64151 FASTENER VELCRO NOMEX LOOP 1000 BACKING 039 GID: BFCBXX
MANF: VELCRO CORP SPEC: MIL-F-21840T1C1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	V 00024.64	

TOXICITY

61270 FASTENER VELCRO NOMEX LOOP 2000 BACKING 0199 GID: BFCBXX
MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.115		00.27	12.00	T NONE
B	1	023.8	014.5	0.105		00.39	10.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.8E-7	2.55	.00		72H-70F-

ODOR

RT	RT WEIGHT	CURE
A	A 00010.27	

TOXICITY

60450 FASTENER VELCRO NOMEX LOOP 2000 BACKING 0399 GID: BFCBXX
MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.100			12.00	T MOD
A	1	023.8	014.5	0.108			02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	7.8E-7	2.85	.70		

ODOR

RT	RT WEIGHT	CURE
A	A 00010.15	

TOXICITY

60466 FASTENER VELCRO NOMEX LOOP 2000 BACKING 1299 GID: BFCBXX
MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.110			02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.8E-7	2.59	.00		

ODOR

RT	RT WEIGHT	CURE
A	V 00010.00	

TOXICITY

60456 FASTENER VELCRO NOMEX LOOP 2000 BACKING 2699 GID: BFCBXX
MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.105		00.47	12.00	T SMALL
I	1	023.8	014.5	0.110		00.27	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-7	2.36	.05		60H-70F-

ODOR

RT	RT WEIGHT	CURE
A	A 00010.04	

TOXICITY

MSFC-HDBK-527 REV F 9999942 0005625 8

Information Handling Services, 2000

60963 FASTENER VELCRO NOMEX LOOP 2000 BACKING 2899 GID: BFBVXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.105			04.30	SMALL
I	1	023.8	014.5	0.108		00.21	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	7.8E-7	3.91	.80		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00009.98	

60462 FASTENER VELCRO NOMEX LOOP 2000 BACKING 9999 GID: BFCBXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.105		00.28	12.00	T SMALL
B	1	023.8	014.5	0.108		00.09	07.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.30	.05		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00010.02	

63251 FASTENER VELCRO NOMEX LOOP 2000 WITH PS 0372 ADHESIVE GID: BOXXXX

SPEC: P/N 194260

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.100			01.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60943 FASTENER VELCRO NOMEX LOOP FR 0327 PRECOAT GID: BOBVXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.100			00.20	NONE
C	1	025.9	014.3	0.100		00.21	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.56	2.35	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.68	

63272 FASTENER VELCRO NYLON 100 BACKING 0172AB GID: BFBSXX

SPEC: P/N 100-001-012-0172AB

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.125		00.34	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06455 FASTENER VELCRO NYLON HAQ 12-2-100 LOOP GID: BOBSXX

SPEC: MIL-F-21840T1C2

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.060			00.46	NONE
A	1	025.9	014.3				02.00	NONE
A	1	030.0	019.0	0.060			00.62	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00218.90	

61687 FASTENER VELCRO NYLON HOOK 0100 GID: DOBVXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.250			02.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005626 T

61687 FASTENER VELCRO NYLON HOOK 0100 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.300			04.60	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.13	1.70	.00	336H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

06298 FASTENER VELCRO NYLON HOOK 2 INCH GID: BOBSXX

MANF: VELCRO CORP SPEC: ST17N060-03

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.1E-6	1.87	.04		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

65419 FASTENER VELCRO NYLON HOOK 65 GID: BOXXXX

MANF: VELCRO CORP SPEC: EH32 (83-256) MIL-F-21840T1C1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	1.90	.30	1.32	

ODOR

RT	RT	WEIGHT	CURE
	K	00027.10	

TOXICITY

61908 FASTENER VELCRO NYLON HOOK 65 AND LOOP 1000 BACKING 0199 GID: BFBSXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.0E-7	1.59	.04		

ODOR

RT	RT	WEIGHT	CURE
A	A	00010.06	

TOXICITY

61901 FASTENER VELCRO NYLON HOOK 65 BACKING 0199 GID: BOBSXX

MANF: VELCRO CORP SPEC: ST17N060

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.070			08.30	MOD
X	2	025.9	014.3	0.067		00.16	12.00 T	MOD
X	1	025.9	014.3	0.067		00.37	12.00 T	MOD
X	1	030.0	009.0	0.070		00.41	12.00 T	MOD
X	1	030.0	009.0	0.100		00.13	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.35	.02		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.34	

TOXICITY

61903 FASTENER VELCRO NYLON HOOK 65 BACKING 0399 GID: BFBVXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.075		00.64	12.00 T	MOD
I	1	023.8	014.5	0.070		00.63	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.82	1.93	.00	

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.12	

TOXICITY

60473 FASTENER VELCRO NYLON HOOK 65 BACKING 2699 GID: BFBVXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.073		00.31	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005627 1

60473 FASTENER VELCRO NYLON HOOK 65 BACKING 2699 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.070		00.40	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.8E-7	2.15	.01		72H-70F-

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
A	A	00019.96	

61900 FASTENER VELCRO NYLON HOOK 65 BACKING 9999 GID: BFBVXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.075			05.20	SMALL
I	1	023.8	014.5	0.681		04.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.8E-7	2.42	.00		

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
A	A	00009.96	

60674 FASTENER VELCRO NYLON HOOK 65 BACKING FR8299 GID: BOBSXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.077			02.70	MOD
X	1	025.9	014.3	0.097			02.40	MOD
X	1	030.0	009.0	0.097			03.90	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.0E-6	3.44	.05	1.44	

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
A	A	00019.43	

64156 FASTENER VELCRO NYLON HOOK 65 BACKING PS 0100 GID: DZBSXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.097	0.003		00.10	NONE
X	1	025.9	014.3	0.097	0.003	00.32	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.8E-6	5.25	1.74	1.03	

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
A	A	00010.57	

61127 FASTENER VELCRO NYLON HOOK 65 BACKING PS 0102 GID: BOXXXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.070	0.003		01.00	MOD
X	1	025.9	014.3	0.070	0.003	00.38	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.06	2.26	.00	

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
A	K	00010.89	

60863 FASTENER VELCRO NYLON HOOK 65 BACKING PS 0107

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.080	0.020	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	V	00010.03	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005628 3

61398 FASTENER VELCRO NYLON HOOK 65 LOOP 1000 BACKING 0399 GID: BFBSXX

MANF: VELCRO CORP

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
		023.8	014.5					NONE	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.0E-6	6.06	2.26	.00		A	K	00010.40	

61397 FASTENER VELCRO NYLON HOOK 65 LOOP 1000 BACKING 1299 GID: BFBSXX

MANF: VELCRO CORP

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	023.8	014.5	0.070		00.30	12.00	T NONE	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	7.8E-7	2.94	.00			A	V	00010.45	

64155 FASTENER VELCRO NYLON HOOK 65 LOOP 1000 BACKING 2699

MANF: VELCRO CORP

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
		023.8	014.5					NONE	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	8.0E-7	1.77	.05			A	K	00010.33	

61391 FASTENER VELCRO NYLON HOOK 65 LOOP 1000 BACKING 2899 GID: BFBSXX

MANF: VELCRO CORP

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	0.075			04.70	MOD	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.0E-6	4.03	1.29	.00		A	K	00010.05	

61390 FASTENER VELCRO NYLON HOOK 65 LOOP 1000 BACKING 9999 GID: BOBSXX

MANF: VELCRO CORP

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
		023.8	014.5					NONE	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	1.0E-6	1.04	.06			A	V	00009.83	

60864 FASTENER VELCRO NYLON HOOK 65 WITH PS 0104 ADHESIVE GID: BOBSXX

MANF: VELCRO CORP SPEC: MIL-F-21840T1C1

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.030			00.10	NONE	No test data	No test data							
A	1	023.8	014.5	0.115			01.30	NONE									
A	1	023.8	014.5	0.075	0.020	00.00	00.00	NONE									
B	2	025.9	014.3	0.073	0.003		00.30	NONE									
B	1	025.9	014.3	0.073	0.003		07.00	SMALL									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	1.8E-6	2.04	.15	.95			A	00007.59	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005629 5

60896 FASTENER VELCRO NYLON HOOK 65 WITH PS 0140 ADHESIVE GID: BOBSXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	023.8	014.5	0.075	0.020	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00010.05	168H-70F-

61036 FASTENER VELCRO NYLON HOOK 65 WITH PS 0172 ADHESIVE GID: BOBSXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.075	0.003	00.13	12.00	T MOD
C	2	030.0	010.0	0.080	0.003	00.04	00.80	NONE
C	1	030.0	010.0	0.080	0.003	00.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.63	.10	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00022.53	

65420 FASTENER VELCRO NYLON HOOK 66 NON MELTING ARAMID GROUND GID: BOXXXX

MANF: VELCRO CORP SPEC: MIL-F-21840T1C2

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	5.27	.79	2.90	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

64154 FASTENER VELCRO NYLON HOOK 80 GID: BFBSXX

MANF: VELCRO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00012.40	

61910 FASTENER VELCRO NYLON HOOK 80 BACKING 0104 GID: BFBVXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	030.0	010.4	0.080	0.003		10.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.4E-6	.36	.09		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

61039 FASTENER VELCRO NYLON HOOK 80 BACKING 0199W GID: BOBSXX

MANF: VELCRO CORP SPEC: MIL-F-21840C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.070		00.55	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-6	2.07	.05	1.31	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00019.57	

60911 FASTENER VELCRO NYLON HOOK 80 WITH PS 0172 GID: BOBSXX

MANF: HARTWELL CORP SPEC: MIL-F-21840T2C1
VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.085		02.90	12.00	T MOD
I	1	025.9	014.3	0.080	0.010	00.07	09.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005630 1

60911 FASTENER VELCRO NYLON HOOK 80 WITH PS 0172 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.090	0.003	00.01	12.00	T SMALL
C	1	030.0	010.0	0.090	0.003	00.01	12.00	T SMALL

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00024.07	

TOXICITY

63270 FASTENER VELCRO NYLON HOOK ADHESIVE BACK GID: BFBSXX

MANF: VELCRO CORP SPEC: P/N 100-080-012-0100AB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.125		00.38	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

00020 FASTENER VELCRO NYLON HOOK AND LOOP GID: BOCDXX

MANF: VELCRO CORP SPEC: MIL-F-21840

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.010		00.09	12.00	T MOD
X	1	025.9	014.3	0.010		00.31	12.20	T MOD
X	2	025.9	014.3	0.070		00.08	11.60	T MOD
X	1	025.9	014.3	0.070		00.40	11.60	T MOD
X	1	025.9	014.3	0.125		00.14	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.49	.16	1.44	24H-241F-0psiaVACUUM

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63278 FASTENER VELCRO NYLON HOOK AND LOOP 65 BACKING 0399 GID: BOXXXX

MANF: VELCRO CORP SPEC: MIL-F-21840ET1C2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.125			02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60906 FASTENER VELCRO NYLON HOOK AND LOOP 80 BACKING PS 0172 GID: BOBSAK

MANF: HARTWELL CORP SPEC: MIL-F-21840T2C1
VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.210	0.010		06.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00020.09	

TOXICITY

60457 FASTENER VELCRO NYLON HOOK AND LOOP WITH FR127A ADHESIVE GID: BOBSBG

MANF: VELCRO CORP SPEC: MIL-F-21840

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.165	0.010	00.09	12.00	T MOD
X	1	023.8	014.5	0.165	0.032	00.06	12.00	T MOD
X	1	023.8	014.5	0.168	0.050		06.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61658 FASTENER VELCRO NYLON HOOK HI-MEG GID: BOBVXX

MANF: VELCRO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.1E-6	2.18	.10	1.74	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005631 3

60971 FASTENER VELCRO NYLON HOOK NOMEX GROUND TAPE WITH FR 0327 PRECOAT GID: BOBVXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.070			00.90	NONE
X	1	025.9	014.3	0.070		00.40	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.6E-6	5.00	1.60	1.67	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.15	

61091 FASTENER VELCRO NYLON KRAYTON LOOP 1000 PS 0102 GID: BOHDXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.085	0.003	00.07	12.00	T MOD
X	1	025.9	014.3	0.085	0.003	00.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	3.46	.45	1.21	

ODOR

RT
X

TOXICITY

RT	RT WEIGHT	CURE
A	00018.85	

62205 FASTENER VELCRO NYLON LOOP 2000 PS 0104 GID: OBSXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.125	0.030		01.00	NONE
A	1	023.8	014.5	1.000	0.030	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60976 FASTENER VELCRO NYLON LOOP 100 BACKING 0199 GID: BOBSXX

SPEC: MIL-F-21840C1 P/N 200-001-012-0199W

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.115		00.48	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.24	.12		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.08	

65421 FASTENER VELCRO NYLON LOOP 1000 GID: BOXXXX

SPEC: MIL-F-21840C1

MANF: VELCRO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	1.74	.24	1.20	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

61902 FASTENER VELCRO NYLON LOOP 1000 BACKING 0199 GID: BFBVXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.110		00.57	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61904 FASTENER VELCRO NYLON LOOP 1000 BACKING 0399 GID: BFBVXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.110		00.58	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61906 FASTENER VELCRO NYLON LOOP 1000 BACKING 1299 GID: BFBVXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.115		00.74	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005632 5

61905 FASTENER VELCRO NYLON LOOP 1000 BACKING 2699 GID: BFBVXX

MANF: VELCRO CORP

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	0.115		00.65	12.00	T MOD	No test data		No test data						

61907 FASTENER VELCRO NYLON LOOP 1000 BACKING 2899 GID: BFBVXX

MANF: VELCRO CORP

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	0.110		00.43	12.00	T MOD	No test data		No test data						

60884 FASTENER VELCRO NYLON LOOP 1000 BACKING PS 0107 GID: BOBSXX

MANF: VELCRO CORP SPEC: P/N 1000-001-0107AA

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.115	0.020	00.00	00.00	NONE	No test data		No test data						

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	00010.06	

60965 FASTENER VELCRO NYLON LOOP 1000 FR 8299 GID: BOXXXX

MANF: VELCRO CORP SPEC: P/N 1000-001-012-8299RA P/N 1000-001-330-8299RA

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.085			02.90	SMALL	No test data		No test data						
A	1	025.9	014.3	0.067			04.50	NONE									
A	1	030.0	009.0	0.104			03.70	SMALL									
A	1	030.0	009.0	0.067			05.10	NONE									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	2.0E-6	4.50	.32	1.50		X	A	00020.62	

61045 FASTENER VELCRO NYLON LOOP 1000 PS 0100 GID: BODTXX

MANF: VELCRO CORP SPEC: MIL-F-21840C1

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
C	2	025.9	014.3	0.097	0.003		00.20	NONE	No test data		No test data						
C	1	025.9	014.3	0.097	0.003	00.29	12.00	T SMALL									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	1.8E-6	2.68	.49	.32		A	A	00018.05	

61676 FASTENER VELCRO NYLON LOOP 1000 PS 0140 GID: BOBSXX

MANF: VELCRO CORP

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
I	2	023.8	014.5	0.115	0.020		00.20	NONE	No test data		No test data						

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							B	00010.09	168H-70F-

60878 FASTENER VELCRO NYLON LOOP 1000 WITH PS 0104 ADHESIVE GID: BOBSXX

MANF: VELCRO CORP SPEC: MIL-F-21840C1

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
I	2	023.8	014.5	0.105	0.020	00.00	00.00	NONE	No test data		No test data						

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005633 7

60878 FASTENER VELCRO NYLON LOOP 1000 WITH PS 0104 ADHESIVE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.115	0.003		00.40	SMALL
B	1	025.9	014.3	0.115	0.003	00.11	08.50	SMALL
I	1	030.0	010.4	0.080		00.12	12.00 T	SMALL
A	1	030.0	010.4	0.120		00.13	06.00	SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.0E-6	2.43	.09	1.29	

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00008.21	

61037 FASTENER VELCRO NYLON LOOP 1000 WITH PS 0172 ADHESIVE GID: BOBSXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.115		00.63	12.00 T	MOD
X	1	024.5	014.3	0.125	0.003	00.03	12.00 T	MOD
X	1	025.9	014.3	0.103	0.003	00.12	12.00 T	MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.73	.30	.99	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00020.63	

60939 FASTENER VELCRO NYLON LOOP 200 BACKING 0199 GID: BOBSXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	009.0	0.125		00.79	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63268 FASTENER VELCRO NYLON LOOP 200 PS 3072 GID: BOXXXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.125			03.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80099 FASTENER VELCRO NYLON LOOP 2000 BACKING 0172 GID: BOBSXX

SPEC: P/N 2000-001-750-0172AB P/N 2000-1000-330-0172

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.110	0.003	00.10	12.00 T	SMALL
X	1	030.0	010.0	0.130	0.003		02.60	MOD
X	2	030.0	010.0	0.150	0.003	00.10	12.00 T	MOD
X	1	030.0	010.0	0.150	0.003	00.10	12.00 T	MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00022.05	

65084 FASTENER VELCRO NYLON LOOP SJ3418 AND HOOK SJ3419B

MANF: 3M CO
VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.005	0.003		04.00	MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00034.26	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005634 9

20320 FASTENER VELCRO NYLON LOOP V22-90-W48 BACKING URETHANE FOAM GID: DYBVCQ

MANF: VELCRO CORP SPEC: ST17N064-02

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.120		00.24	12.00	T MOD	No test data	No test data					
X	1	025.9	014.3	0.120		00.50	12.00	T MOD							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	1.0E-6	1.24	.15			A	A	00022.37	

60458 FASTENER VELCRO NYLON LOOP WITH FR127 ADHESIVE GID: BNBSBG

MANF: VELCRO CORP SPEC: MIL-F-21840

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	0.121	0.010	00.12	12.00	T MOD	No test data	No test data					

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.0E-6	8.22	7.18	.00		No test data			

06611 FASTENER VELCRO NYLON LOOP WITH PS 0102 ADHESIVE GID: ABCDXX

MANF: VELCRO CORP SPEC: P/N 001-130-0102

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.120	0.003		01.30	MOD	No test data	No test data					
X	1	025.9	014.3	0.120	0.003	00.41	12.00	T MOD							
X	2	025.9	014.3	0.130		00.00	00.00	NONE							
X	1	025.9	014.3	0.130			02.10	MOD							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.3E-6	4.08	1.28	1.11		A	A	00020.08	

80276 FASTENER VELCRO PEEK HOOK AND LOOP GID: BOXXXX

MANF: VELCRO CORP

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
I	1	030.0	010.0	0.117		0.6	12.00	T NONE	No test data	No test data					
I	1	030.0	010.0	0.109		0.6	12.00	T NONE							
I	1	030.0	010.0	0.142		0.6	12.00	T NONE							

61174 FASTENER VELCRO POLYESTER HOOK 1 INCH GID: DYCBXX

MANF: VELCRO CORP SPEC: ST13H819-02

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	6.0E-6	2.01	.01			No test data			

60463 FASTENER VELCRO POLYESTER HOOK 80 BACKING 0199 GID: BFCBXX

MANF: VELCRO CORP

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	0.075		00.57	12.00	T MOD	No test data	No test data					
X	1	025.9	014.3	0.070		00.75	12.00	T MOD							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	1.0E-6	2.18	.78	.15		A	A	00020.56	

60603 FASTENER VELCRO POLYESTER HOOK 80 BACKING FR8299 GID: BOXXXX

MANF: VELCRO CORP

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005635 0

60603 FASTENER VELCRO POLYESTER HOOK 80 BACKING FR8299 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.065			03.70	MOD
X	1	030.0	009.0	0.065			03.80	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.8E-6	3.21	.06	1.07	

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE
K	00010.05	

62090 FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 0199 GID: BFCBXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.59	.01	1.72	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00010.35	

62091 FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 0399 GID: BFCBXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.79	1.21	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00010.07	

62092 FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 1299 GID: BFCBXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.92	.05	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00009.82	

62088 FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 2699 GID: BFCBXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	8.0E-7	.37	.02		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00010.13	

62087 FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 2899 GID: BFCBXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.0E-7	1.56	.82		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00010.40	

62089 FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 9999 GID: BFCBXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005636 2

62089 FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 9999 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.26	.11	.00	

ODOR

RT	RT	WEIGHT	CURE
A	A	00010.41	

TOXICITY

61041 FASTENER VELCRO POLYESTER HOOK 80 WITH FR PS 8222 GID: BDCBXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.085			03.80	MOD
X	2	025.9	014.3	0.070	0.003		02.10	MOD
X	1	025.9	014.3	0.070	0.003		07.70	MOD
B	2	025.9	014.3	0.087	0.003		01.00	NONE
B	1	025.9	014.3	0.087	0.003		06.20	SMALL
A	1	030.0	010.0	0.120		00.63	04.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.4E-6	4.27	.77	.80	

ODOR

RT	RT	WEIGHT	CURE
	X	00022.74	

TOXICITY

60985 FASTENER VELCRO POLYESTER HOOK 80 WITH Y966 TAPE GID: BOCBXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.100	0.010	00.30	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00001.20	

TOXICITY

03433 FASTENER VELCRO POLYESTER HOOK H549 GID: BNCBXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.085		0.16	01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.4E-7	.46	.01		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

61417 FASTENER VELCRO POLYESTER HOOK H549 FR127A ADHESIVE GID: BNCBBG

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.096	0.004	00.10	12.00 T	NONE
I	1	023.8	014.5	0.136	0.050	00.12	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20470 FASTENER VELCRO POLYESTER HOOK H592 GID: BOCBXX

MANF: VELCRO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.18	.73	.00	24H-150F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

61040 FASTENER VELCRO POLYESTER LOOP 1000 FR PS 8222 GID: BOCBXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.125			04.30	MOD
X	2	025.9	014.3	0.115	0.003	00.05	12.00 T	MOD
X	1	025.9	014.3	0.115	0.003	00.22	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005637 4

61040 FASTENER VELCRO POLYESTER LOOP 1000 FR PS 8222 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
X	1	025.9	014.3	0.125	0.003		05.30		MOD
X	2	030.0	010.4	0.125	0.003	00.46	12.00	T	MOD
X	1	030.0	010.4	0.125	0.003	00.20	12.00	T	MOD
X	1	030.0	010.0	0.120		00.56	02.00		MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.4E-6	4.31	.74	.75	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00026.80	

65451 FASTENER VELCRO POLYESTER LOOP 192822/HOOK 192832 GID: BNXXXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
X	1	025.9	014.3	0.080		00.90	12.00	T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.73	.12	.17	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

61067 FASTENER VELCRO POLYESTER LOOP 2000 GID: BOBSXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
X	1	025.9	014.3	0.100		00.61	12.00	T	MOD
X	1	030.0	010.0	0.081		01.10	12.00	T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.97	.83	.12	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00020.10	

60447 FASTENER VELCRO POLYESTER LOOP 2000 BACKING 1299

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
I	1	023.8	014.5	0.105		00.76	12.00	T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60870 FASTENER VELCRO POLYESTER LOOP 2000 WITH Y966 TAPE GID: BOCBXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
X	1	030.0	010.0	0.100	0.010	00.13	02.70		MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00013.37	

80101 FASTENER VELCRO STILAN HOOK BACKING 0399 AND POLYESTER LOOP 2000 BACKING 0399

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
I	1	030.0	010.0	0.106		00.80	12.00	T	NONE
B	1	030.0	010.0	0.149		00.40	11.90		NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	1.25	.51	.05	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	22.045	

80100 FASTENER VELCRO STILAN HOOK BACKING 8299 AND POLYESTER LOOP 2000

MANF: VELCRO CORP

MSFC-HDBK-527 REV F 9999942 0005638 6

Information Handling Services, 2000

80100 FASTENER VELCRO STILAN HOOK BACKING 8299 AND POLYESTER LOOP 2000 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.154		00.50	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80098 FASTENER VELCRO STILAN HOOK WITH BINDER ADHESIVE 0399

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.076			04.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	1.28	.52	.09	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	21.880	

80254 FASTENER VELCRO STILAN LOOP 0399 GID: BOXXXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.027			03.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65458 FASTENER VELCRO STILAN POLYESTER HOOK/ASTRO GID: BOHLXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.080			02.90	SMALL
X	1	100.0	020.2	0.080		01.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	6.0E-6	.34	.02	.13	24H-70F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00029.27	24H-70F-

60999 FASTENER VELCRO VELCOIN 1000 PS 0107 GID: BNBVXX

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.075			03.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00006.28	

62925 FEEDTHRU CONNECTOR KYNAR/SS GID: BCCTKW

MANF: GLENAIR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3				00.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20037 FELT ASBESTOS GID: BIFLXX

MANF: JOHNS-MANVILLE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	500		250	0.022	0	20
B	MECH	500	72	250	0.022	0	20
B	MECH	500	72	70	0.020	0	20
B	PNEU	500		70	0.022	0	20

06419 FELT BETA GLASS C3-21-109 GID: B1XXXX

MANF: OWENS CORNING

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005639 8

60165 FELT DACRON/POLYESTER/FIBREDYN GID: BICBXX

....NO TEST DATA AVAILABLE....

05508 FELT MICROFIBER TYPE E 4-6 LBS GID: BIFVXX

MANF: JOHNS-MANVILLE

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.173		00.00	00.00	NONE	No test data		No test data						

THERMAL VACUUM STABILITY					ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.15	.00	.00		No test data		

20742 FELT NOMEX GID: BIBVXX

MANF: DRYCORE FELT CO
STERN & STERN

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	3.61	.04	.00		No test data		

20344 FELT NOMEX 4.5 OZ/SQ YD GID: BIXXXX

MANF: FABRIC RESEARCH LAB

....NO TEST DATA AVAILABLE....

61941 FELT NOMEX 61HT/14 GID: BIBVXX

MANF: GAF CORP

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
C	2	025.9	014.3	0.075			00.20	NONE	No test data		No test data						
C	1	025.9	014.3	0.075		00.17	12.00	T NONE									

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-7	3.88	.07			A	A 00029.77	

20154 FELT NOMEX 62HT/14 GID: BIBVXX

MANF: AMERICAN FELT & FILTER

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	9.0E-7	3.00	.11			A	A 00026.02	

05105 FELT NOMEX NON-WOVEN GID: BIBVXX

MANF: FABRIC RESEARCH LAB SPEC: MB0135-051T2

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
C	2	025.9	014.3	0.150			00.20	NONE	No test data		No test data						
C	1	025.9	014.3	0.150		00.12	12.00	T NONE									

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	4.2E-6	1.75	.10	1.15		A	A 00019.84	

61419 FELT NOMEX S2335 NRB/Z GID: BIBVXX

MANF: GLOBE ALBANY CORP SPEC: MB0135-051T2C1

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.175			03.80	NONE	No test data		No test data						
I	1	023.8	014.5	0.084		00.23	04.50	T NONE									

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	3.7E-6	1.14	.00				B 00016.02	24H-150F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005640 4

61697 FELT NOMEX STYLE 190R GID: BIBSXX
MANF: GLOBE ALBANY CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	2.94	.12	.00	

ODOR

RT	RT WEIGHT	CURE
A	X 00061.06	

TOXICITY

20483 FELT NOMEX STYLE 22NX GID: BIBVXX
MANF: DUPONT
SPEC: FED STD 191

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.130			00.30	NONE
C	1	025.9	014.3	0.130		00.36	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.2E-6	4.08	.01	2.64	

ODOR

RT	RT WEIGHT	CURE
A	K 00019.56	

TOXICITY

05513 FELT NOMEX/DC92-007 SILICONE COATED GID: BICKBV
MANF: ALBANY INTERNATIONAL
DOW CORNING
QSL
SPEC: MB0135-056

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.400	0.052		00.80	NONE
I	1	023.8	014.5	0.375		00.11	12.00	T NONE
I	1	023.8	014.7	0.400	0.052	00.03	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.9E-6	1.05	.00		SEE TEST REPORT

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05514 FELT NOMEX/SILICONE COATED GID: BIBVCK
MANF: ROCKWELL
SPEC: MB0130-119
MB0135-058T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	021.0	014.7	0.150		00.19	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06097 FELT REFRASIL B100 SILICA GID: BIXXXX
MANF: HITCO
....NO TEST DATA AVAILABLE....

05018 FELT SILICA FI600 GID: BIXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.60	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05737 FELT TECKFELT 45-09811 GID: BICKXX
MANF: TECHNICAL WIRE PROD
SPEC: MIL-S-23586

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.031			01.90	NONE
A	1	030.0	010.0	0.060			06.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.6E-7	.59	.29		48H-212F-0psia5E-6

ODOR

RT	RT WEIGHT	CURE
	A 00106.55	

TOXICITY

20495 FELT TFE GID: BICNXX
MANF: DUPONT
SPEC: ST10F071-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005641 6

20495 FELT TFE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	033.0	014.3	0.075			09.70	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.4E-7	.32	.00		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.22	

TOXICITY

62926 FELT UL94HBF/C430 ADHESIVE BACK GID: BIXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.375	0.100		02.50	NONE
I	1	020.9	014.7	0.375		00.16	08.00 T	NONE
I	1	025.9	014.3	0.375		00.40	08.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20051 FELT WOOL GID: BIXXXX

MANF: AQM SPEC: AMS 3285 C-F-206

....NO TEST DATA AVAILABLE....

05856 FERRITE FERROXCUBE 3C8 INORGAN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.00	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20125 FIBER HE1051 GLASS/ACRY BIND GID: BFGDXX

MANF: HOLLINGSWORTH & VOSE

....NO TEST DATA AVAILABLE....

62816 FIBER OPTICS SENSOR PROBE

MANF: MECHANICAL TECHNOLOGY INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	400	72	-297	0.065	5	10

62927 FIBERGLASS ON FILM ALUM/TEDLAR GID: BPGDCJ

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.004		00.40	12.00 T	NONE
B	1	020.9	014.7	0.004			07.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64287 FIBERGLASS/EPOXY EF2/59

MANF: BASD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.8E-6	.14	.00	.08	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20145 FIBRE VULCANIZED GRADE CH

MANF: H H SMITH SPEC: MIL-F-1148

....NO TEST DATA AVAILABLE....

62733 FILA WOUND CASE COMP/SEALER GID: EXXXXX

MANF: HERCULES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.375		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005642 8

62734 FILA WOUND CASE COMPONENTS GID: EXXXXX
MANF: HERCULES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.375		00.00	00.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05350 FILAMENT LRF205 EPOXY KEVLAR 49 GID: BBBGJH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.34	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20141 FILLER ACTROFILL 1241 GID: DDXXXX
MANF: ACTRONICS INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-6				

ODOR

RT	RT WEIGHT	CURE
A	00020.04	

TOXICITY

62928 FILLER CORFIL 615 EPOXY GID: DDBGXX
MANF: AMERICAN CYANAMID SPEC: MT3-13-1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.3	0.125		00.05	06.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	1.74	1.29	.00	2H-351F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60287 FILLER MATERIAL ECCOSPHERES SI GID: ABBGXX
MANF: EMERSON AND CUMING SPEC: USB-MS-9002
....NO TEST DATA AVAILABLE....

61165 FILM 2104 PLASTIC GID: DUXXXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.003			08.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65171 FILM 2481 INFRARED (135-36) GID: BSBNXX
MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00027.41	

TOXICITY

64923 FILM 43/82/2 KAPTON/NOMEX/AU GID: BPCDBV
MANF: NATIONAL METALLIZING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.009		02.10	06.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65312 FILM 8019,8020 WITH 8060 LABEL GID: BPBYCB
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
V	00010.73	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005643 T

65245 FILM 8210 WITH 8060 LABEL GID: BPBYCB
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00010.13	

60755 FILM ACLAR 2100 GID: BPEFXX
MANF: ALLIED CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.079	2	05
B	MECH	1500	72	70	0.079	0	20
X	PNEU	1500		70	0.079	01	01
B	PNEU	250		70	0.079	0	20
X	PNEU	500		70	0.079	1	20
Z	MECH	5000	25	70	0.079	1	6

60725 FILM ACLAR 22A GID: BPEFXX
MANF: ALLIED CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002			02.40	NONE
A	1	025.9	014.3	0.002			02.40	NONE
X	1	030.0	009.0	0.002			03.80	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00011.93	

06255 FILM ACLAR 33C ECTFE GID: BPBDXX
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

01267 FILM ACLAR 33F CTFE GID: AKXXXX
MANF: ALLIED CHEMICAL SPEC: AMS 3649

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005			02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70	0.005	0	20
B	MECH	1500	72	70	0.005	0	20
I	PNEU	1500		70	0.005	1	20

62891 FILM ACLAR 933A GID: BPXXXX
MANF: ALLIED CHEMICAL SPEC: MMS-Y-933A000
SCIENTIFIC ENTERPRISES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.002	0	20
B	MECH	14.7	72	-297	0.005	0	20

20208 FILM ADHESIVE XT40 110/234 GID: BPBGXX
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.55	1.26	.00	1H-165F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05034 FILM AL/TEDLAR/NYLON AN16 GID: BPFJBS
MANF: ORCON CORP SPEC: DMS 2072C T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.005			00.88	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005644 1

05034 FILM AL/TEDLAR/NYLON AN16 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.005			04.30	NONE
I	1	023.8	014.5	0.005		01.80	12.00	T NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.81	1.57	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	A 00001.30	

80293 FILM ANTI-STATIC WITH GRIDS GID: BPXXXX

MANF: BAYSTAT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.007		0.31	11.50	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61339 FILM BONDING XC453 GID: BPXXXX

MANF: 3M CO SPEC: MB0120-070 T2C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.007	0.003		03.90	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63726 FILM CAPRAN 518 GREEN GID: BPBSXX

MANF: ALLIED CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002		01.42	04.97	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62929 FILM CAPRAN 980 NYLON GID: BPBSXX

MANF: ALLIED CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003			04.10	NONE
A	1	025.9	014.3	0.003			04.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	8.0E-7	3.48	.00	3.09	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

06580 FILM CAPRON 80 GID: BPBYVY

MANF: ALLIED CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002			05.10	NONE
C	1	025.9	014.3	0.002		01.28	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	2.58	.02	2.26	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	A 00008.40	

60490 FILM CMC122 KAPTON ADHESIVE COATED GID: BPXXXX

MANF: CIRCUIT MATERIALS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.2E-6	.59	.14		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

61707 FILM CMC8-14-1A POLYIMIDE GID: BPCDXX

MANF: EXXON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	X 00002.28	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005645 3

64282 FILM COLORSLIDE 1000/135-36 GID: BSXXXX
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00032.11	

TOXICITY

80093 FILM COPPER/MYLAR GID: BPHNXX
MANF: TAPECON SPEC: LAC24-4760

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.004		01.70	12.00	T MOD

FSC

RT	FLUID NAME
A	GENETRON 502

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.06	.04	.00	

ODOR

RT	RT WEIGHT	CURE
A	A 21.841	

TOXICITY

80172 FILM CR39 GID: BPXXXX
MANF: SAN FRANCISCO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	X 2.235	

TOXICITY

80202 FILM CRONALAR HIGH ACUTANCE HA4 CRONAR CLEAR POLYESTER HIGH CONTRAST NEGATIVE WORKING FILM GID: BPXXXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.008		0.1	12.00	T SMALL
C	1	030.0	010.0	0.008		0.9	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	K 21.528	

TOXICITY

80203 FILM CRONALAR HIGH ACUTANCE HA7 CRONAR CLEAR POLYESTER HIGH CONTRAST NEGATIVE WORKING FILM GID: AKXXXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.008		00.09	12.00	T SMALL
C	1	030.0	010.0	0.008		0.8	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	K 21.666	

TOXICITY

80192 FILM CRONAPAQUE CPF7 WHITE SEMI-OPAQUE GID: BPXXXX
MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	K 21.233	

TOXICITY

61848 FILM CRONOPAQUE PETP/VINYL GID: BSCCCV
MANF: NASA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.008		00.90	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80198 FILM CRP POLYETHYLENE ANTISTATIC P/N B0214 GID: BPCFXX
MANF: CLEAN ROOM PRODUCTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	.66	.29	.01	

ODOR

RT	RT WEIGHT	CURE
A	K 22.372	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005646 5

60759 FILM CUPRON PMPX-C .0002" GID: BPXXXX
MANF: PHOTOFABRICATION TECNOLOGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.2E-6	.06	.05	.01	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

65117 FILM EKTACHROME 200 GID: BSXXXX
MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00025.94	

TOXICITY

64092 FILM EKTACHROME EE2241 (4001) GID: BSXXXX
MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00356.00	

TOXICITY

80210 FILM EKTACHROME SO251 HIGH SPEED VIDEO NEWS GID: BSXXXX
MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	2.908	

TOXICITY

63642 FILM EKTACHROME VIDEO NEWS
MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	X	03821.30	

TOXICITY

60600 FILM EKTACHROME VIDEO TY 4250 GID: BSXXXX
MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00141.11	

TOXICITY

65269 FILM EKTAPRINT ON E20 PAPER GID: BPGMXX
MANF: EASTMAN KODAK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		030.0	010.0	0.600				NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00022.59	

TOXICITY

63522 FILM EKTRACHROME 5020 GID: BSXXXX
MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00046.33	

TOXICITY

20091 FILM ELVANOL 71-30 PVA GID: BPXXXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.008		00.04	11.80 T	NONE
C	1	023.8	014.5	0.008		00.76	11.80 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005647 7 ■

20091 FILM ELVANOL 71-30 PVA (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00015.10	

TOXICITY

06359 FILM G099700 VAC DEPOSITED ALUMINUM .5 MIL KAPTON STYLE 108 GLASS FABRIC WITH 3P ADHESIVE GID: BFCDIA

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003			02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	9.0E-6	.47	.02		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06360 FILM G127200 VAC DEPOSITED ALUMINUM .5 KAPTON STYLE 112 GLASS FABRIC WITH 3P ADHESIVE GID: BFFVXX

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003			02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.13	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06052 FILM G145100 .5 MIL KAPTON .9 OZ PER SQUARE YARD NOMEX SCRIM GID: BPCDBV

MANF: SHELDAHL SPEC: BMO135-048 T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.007			02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.21	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62213 FILM G402474 VAL/POLYIMIDE GID: FJCDXX

MANF: SHELDAHL SPEC: MBO135-079T2

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	5.1E-6	1.39	.05		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06503 FILM G412020 KAPTON/ALUMINUM/ORGANIC COATED GID: BPDEFJ

MANF: SHELDAHL SPEC: MBO135-084T1C2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003			01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	1.11	.01	1.06	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64038 FILM G412500 POLYIMIDE/ARAMID GID: DPCDXX

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	15	-297	0.007	01	13

64040 FILM G413200 FEP/POLYIMIDE GID: BPCDXX

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.006	1	2

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005648 9

64039 FILM G414000 POLYIMIDE/GLASS GID: BPCDIA

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	20	-297	0.006	0	20

69901 FILM GORETEX 1/4" TFE PIPE SEALANT WITH ADHESIVE

MANF: W L GORE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.126	0.003		04.60	NONE
I	1	100.0	014.5	0.126	0.003	01.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

69900 FILM GORETEX 1/4" TFE PIPE SEALANT/NONADHESIVE GID: ABBGXX

MANF: FLUOROCARBON CORP
W L GORE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.190			01.50	NONE
I	1	100.0	014.5	0.190		00.50	11.70	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297		00	20

62502 FILM GORTEX LAMIN WITH FABRIC NOMEX GID: BPCNJH

MANF: W L GORE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE
C	HYZE
A	MMH
C	MMH
C	N204

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64103 FILM HS6262 VAC PAK NYLON GID: BPBSXX

MANF: RICHMOND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002		00.62	02.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65249 FILM HS800 VAC PAK NYLON GOLD GID: BPBSXX

MANF: RICHMOND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003			05.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65144 FILM HS8171 VAC PAK NYLON GID: BPBSXX

MANF: RICHMOND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003			04.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20264 FILM HYTUFF MP2080 POLYURETHANE GID: BPCQXX

MANF: STEVENS MOLDED PROD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.005			00.90	SMALL
B	1	023.8	014.5	0.005			06.60	SMALL
X	2	025.9	014.3	0.014		00.20	12.00	T MOD
X	1	025.9	014.3	0.014		00.46	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005649 0

20264 FILM HYTUFF MP2080 POLYURETHANE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00008.11	

64273 FILM KAPAK/SCOTCHPAK GID: BPXXXX

MANF: KAPAK CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00023.69	

64271 FILM KAPTON AL/BETA 107/GLASS GID: BPCDHL

MANF: NATIONAL METALLIZING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.004		00.51	02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20883 FILM KAPTON ALUMINIZED GID: BPFJXX

MANF: NATIONAL METALLIZING
SHELDAHL

SPEC: MB0125-066T1C3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001			02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.95	.02	.35	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05381 FILM KAPTON F150F019 GID: FJCDXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.002			00.20	NONE
A	1	023.8	014.5	0.002			03.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05077 FILM KAPTON GOLDIZED GID: BPXXXX

MANF: SHELDAHL

SPEC: MB0135-038

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	009.0	0.009		01.57	12.00	T NONE

FSC

RT	FLUID NAME
A	GENETRON 502

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.97	.00	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05079 FILM KAPTON GOLDIZED FLOCKED GID: BPXXXX

....NO TEST DATA AVAILABLE....

05786 FILM KAPTON GOLDIZED MMD10038 GID: CKXXXX

....NO TEST DATA AVAILABLE....

05946 FILM KAPTON H GID: DPCDXX

MANF: DUPONT

SPEC: MIL-P-46112

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.001			00.10	NONE
C	1	023.8	014.5	0.001		00.44	10.90	T NONE
A	1	025.9	014.3	0.002			05.50	SMALL
B	1	030.0	009.0	0.002			05.50	SMALL

FSC

RT	FLUID NAME
A	GENETRON 502

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005650 7

05946 FILM KAPTON H (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	030.0	010.0	0.003			02.60		NONE
C	2	030.0	010.0	0.002			00.30	T	NONE
C	1	030.0	010.0	0.002		00.90	12.00	T	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.42	.06	.00	24H-302F-

ODOR

RT	RT	WEIGHT	CURE
A	V	00006.38	

TOXICITY

80252 FILM KAPTON HF POLYIMIDE GID: BPXXXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	GENETRON 502

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

01342 FILM KAPTON POLYIMIDE GID: DPCDXX

MANF: SHELDAHL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.4E-6	.85	.02	.53	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

65086 FILM KAPTON/BETA 107 POLYESTER FR GID: BPCBHL

MANF: NATIONAL METALLIZING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	020.9	014.7	0.004			01.60		NONE
B	2	020.9	014.7	0.040			00.10		NONE
B	1	020.9	014.7	0.040		13.00	06.50		NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65163 FILM KAPTON/CHEMGLAZE/BETA 107 GID: BPCPFV

MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
C	2	020.9	014.7	0.010			00.20		SMALL
C	1	020.9	014.7	0.010		01.60	12.00	T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05504 FILM KAPTON/FEP TEFLON GID: BPCDCN

MANF: DUPONT

....NO TEST DATA AVAILABLE....

64208 FILM KAPTON/GLASS/BETA 107 BLK GID: BPCDHL

MANF: NATIONAL METALLIZING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	020.9	014.7	0.003			02.50		NONE
I	1	030.0	014.7	0.005		03.00	12.00	T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05621 FILM KEMIT 5518 POLYIMIDE/TFE/LUBRICANT GID: BPCDCN

MANF: CHEMPLAST

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
X	2	030.0	010.0	0.001		00.30	12.00	T	NONE
X	1	030.0	010.0	0.001		01.40	12.00	T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.0E-6	.33	.04	.28	

ODOR

RT	RT	WEIGHT	CURE
A	A	2.67	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005651 9

80171 FILM KIMFOIL GID: BPXXXX
MANF: KIMBERLY CLARK CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE.
	K	2.176	

TOXICITY

61359 FILM KODACHROME 64 KR135-36 GID: BSXXXX
MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00022.40	

TOXICITY

69956 FILM KODACOLOR VR-G GID: BPXXXX
MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	22.779	

TOXICITY

62368 FILM KODACOLOR VR/1000 GID: BPXXXX
MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00027.87	

TOXICITY

60760 FILM KODAK 160 COLOR MOVIE GID: BPXXXX
MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	X	00068.16	

TOXICITY

62374 FILM KODAK 7294 HIGH SPEED GID: BPXXXX
MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	V	00019.33	

TOXICITY

62931 FILM KODAK PCF135-36 STYLE2483 GID: BSXXXX
MANF: EASTMAN KODAK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.005			05.00	MOD
X	1	024.5	014.3	0.005			06.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61358 FILM KODAK TX135-36 GID: BPXXXX
MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00029.49	

TOXICITY

64112 FILM KODAR 6763 GID: BPCBXX
MANF: OAK INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.009			01.10	NONE
X	1	030.0	010.0	0.009		00.70	11.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00022.10	

TOXICITY

MSFC-HDBK-527 REV F 9999942 0005652 0

Information Handling Services, 2000

62551 FILM KYNAR NATURAL GID: BPCTXX
MANF: WESTLAKE PLASTICS CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	X	00027.37	

80976 FILM KYNAR NATURAL TOX RATE STUDY
MANF: DOW CORNING
WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

65210 FILM LH94-5 CLEAR GID: BPXXXX
MANF: PERVEL INDUSTRIES SPEC: SP-R-0022A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	1.14	.10	.19	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

60808 FILM LMC300 KAPTON GID: BPCDXX
MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.9E-7	.12	.03		

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

64317 FILM LUMILOR POLYESTER INSULATION GID: BPXXXX
MANF: TORAY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.004		00.50	10.20	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	K	00022.62	

69989 FILM MACTAC XD0002 ADHESIVE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	030.0	010.0	0.002	0.003	00.00	00.00	NONE
B	1	030.0	010.0	0.002	0.003	00.40	08.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.0E-6	2.34	.61	.50	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	A	10.979	

63640 FILM MAGAZINE
MANF: PHOTO-SONICS INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	X	02588.80	

63674 FILM MAGAZINE 16MM
MANF: PHOTO-SONICS INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	K	09080.00	

61253 FILM METLBOND 1113-2 ADHESIVE GID: ACBGXX
MANF: NARMCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.015	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005653 2

61253 FILM METLBOND 1113-2 ADHESIVE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	023.8	014.5	0.015	0.003		12.00	T SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.2E-6	.88	.04		.33H-290F-

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00047.86	.33H-290F-

69814 FILM METPOLY 100

MANF: MARTIN PROCESSING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001			00.25	NONE

FSC

RT	FLUID NAME
X	N204

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65042 FILM MPD2055 50 GAUGE CF GID: DKCFXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	030.0	010.0	0.002		00.80	07.00	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00003.91	

64181 FILM MYLAR "S" GID: BPXXXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	GENETRON 502

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.010	00	20
X	MECH	300.0	20	200	0.010	00	20

60950 FILM MYLAR 105 CLEAR/JCP E20 GID: DPDUGM

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.009		00.08	10.50	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.26	

61295 FILM MYLAR 205 RED/JCP E20 GID: DPDUGM

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.009		00.09	10.50	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.90	

60949 FILM MYLAR 305 YELLOW/JCP E20 GID: DPDUGM

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.009		00.10	10.50	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00020.45	

MSFC-HDBK-527 REV F 9999942 0005654 4

Information Handling Services, 2000

62704 FILM MYLAR 315 LTYEEL/JCP E20 GID: DPDUGM

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.009		00.09	10.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.52	.03	.10	

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.94	

TOXICITY

61296 FILM MYLAR 505 ORANGE/JCP E20 GID: BPDUGM

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.009		00.08	10.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.23	

TOXICITY

61297 FILM MYLAR 615 LT GRN/JCP E20 GID: DPDUGM

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.009		00.09	10.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.63	

TOXICITY

61294 FILM MYLAR 805 PURPLE/JCP E20 GID: DPDUGM

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.009		00.09	10.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.00	

TOXICITY

60951 FILM MYLAR 915 BROWN/JCP E20 GID: DPDUGM

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.009		00.08	10.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.01	

TOXICITY

20384 FILM MYLAR ALUMINIZED GID: DYCBFJ

MANF: NATIONAL METALLIZING

SPEC: ST92M048 ST92M048-01
ST92M048.01 ST92M059-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.006			03.30	NONE
C	1	023.8	014.5	0.006		01.60	12.00	T NONE
X	2	025.9	014.3	0.006		00.32	12.00	T NONE
X	1	025.9	014.3	0.006		02.94	12.00	T NONE
X	2	030.0	010.0	0.006		0.6	12.00	NONE
X	1	030.0	010.0	0.006		7.1	12.00	NONE

FSC

RT	FLUID NAME
A	AMMONIA
X	AMMONIA

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
[illegible]					

ODOR

RT	RT	WEIGHT	CURE
A	X	00000.54	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005655 6

06510 FILM MYLAR DRAFTING 1110 GID: BPXXXX

....NO TEST DATA AVAILABLE....

20582 FILM MYLAR MIRROR REFLECT GID: BPCBXX

MANF: MIRREX CORP SPEC: ST92M954-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	033.0	014.3	1.700		00.17	10.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00219.21	

60134 FILM MYLAR PLASTIC 2 MIL GID: BPXXXX

....NO TEST DATA AVAILABLE....

00701 FILM MYLAR POLYESTER GID: CKPBXX

MANF: DUPONT SPEC: MIL-I-631 MIL-I-631TA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.003		01.35	12.00	T MOD
X	1	030.0	010.0	0.010		00.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	1500	72	70		2	02
B	PNEU	1500		70	0.001	0	20
B	PNEU	1500		70	001	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.9E-6	.13	.00		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00021.94	

05665 FILM MYLAR POLYLOK GID: BPXXXX

MANF: SOLOPAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.66	.45	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

69898 FILM MYLAR SHEET/POLLOK LOCKING ELEMENT GREEN GID: BNCBXX

MANF: REXHAM-INDUSTRIAL FILM DIV.

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.130		0.20	12.00	T LARGE
X	1	030.0	010.0	0.130		0.40	12.00	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.69	.04	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	22.19	

63979 FILM MYLAR TYPE A GID: BPXXXX

MANF: DUPONT SPEC: AMS 3612

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	GENETRON 502

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.009	1	20
B	MECH	50.0	72	72	0.009	00	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.50	.06	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

62930 FILM NM50-13 KAPTON/NOMEX GID: BPCDHS

MANF: NATIONAL METALLIZING SPEC: MB0135-083

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.010			02.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005656 8

62930 FILM HM50-13 KAPTON/NOMEX (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.010		01.05	12.00	T NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.30	.08	.96	

ODOR

RT	RT	WEIGHT	CURE
A	A	00009.04	

TOXICITY

06335 FILM HM50-48 KAPTON/AL/ORGANIC COATED GID: BPCDXX

MANF: NATIONAL METALLIZING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.001		00.00	00.00	NONE
C	1	020.9	014.7	0.001		02.33	11.90	T NONE
I	1	020.9	014.7	0.001		02.00	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	1.01	.04	.64	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

06585 FILM HM50-49 KAPTON GOLDIZED GID: BPCDXX

MANF: NATIONAL METALLIZING SPEC: MB0135-038T1C4

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002			01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.87	.00	.82	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

06336 FILM HM50-67 KAPTON AL/ORGANIC COATED GID: BPFJHS

MANF: NATIONAL METALLIZING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.001		00.00	00.00	NONE
C	1	020.9	014.7	0.001		02.56	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	1.07	.02	.74	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

06448 FILM HM54-15 KAPTON AL/ORGANIC COATED GID: BPCDFJ

MANF: NATIONAL METALLIZING SPEC: MB0135-084T1C2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.2E-6	.86	.01	.66	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

63774 FILM NYEBAR CT FLUOROCARBON BARRIER

MANF: WILLIAM F NYE INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00000.01	

TOXICITY

61175 FILM NYLON GID: BPBVXX

MANF: SPEC: MIL-B-22191T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.002			09.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005657 T

61175 FILM NYLON (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.04	.01	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

65339 FILM NYLON CLEAR 06 GID: BPBSXX

MANF: RICHMOND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.7	0.003			01.70	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	8.0E-7	3.14	.00	3.50	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

63727 FILM NYLON RCAS 2400 ORANGE GID: BPBSXX

MANF: RICHMOND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002		01.04	03.73	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61558 FILM P188-5/1 KAPTON/ACRYLIC GID: BPAKXX

MANF: FRALOCK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.007	0.003		01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00014.05	

62934 FILM PANATONIC X/ACETATE GID: BSXXXX

MANF: EASTMAN KODAK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.006		01.00	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62935 FILM PANATONIC X3400/ESTAR GID: BSXXXX

MANF: EASTMAN KODAK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.003		01.33	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20300 FILM PERFLEX-E POLYURETHANE GID: BPCQXX

MANF: GERING PLASTICS

....NO TEST DATA AVAILABLE....

64011 FILM PHOTO EKTACHROME QX851 GID: BPXXXX

MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	00084.74	

60969 FILM PHOTO EN7 GID: BSXXXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.007		00.08	11.90	T MOD
X	1	025.9	014.3	0.007		01.02	11.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005658 1

60969 FILM PHOTO EN7 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.17	

TOXICITY

60967 FILM PHOTO LP4 GID: BSXXXX

MANF: EASTMAN KODAK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.005		00.07	11.90	T SMALL
C	1	025.9	014.3	0.005		01.01	11.90	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.04	

TOXICITY

60968 FILM PHOTO LP7 GID: BSXXXX

MANF: EASTMAN KODAK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.007			02.50	SMALL
C	1	025.9	014.3	0.007		00.96	11.90	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.00	

TOXICITY

64002 FILM PHOTO PAN 2415 GID: EYBSXX

MANF: EASTMAN KODAK

SPEC: SED33101584-302 SED33101586-302

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00027.63	

TOXICITY

60513 FILM PHOTOGRAPHIC GID: BSXXXX

MANF: EASTMAN KODAK

....NO TEST DATA AVAILABLE....

61095 FILM PHOTOGRAPHIC 107 B & W GID: BSXXXX

MANF: POLAROID

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	X	00140.94	

TOXICITY

61094 FILM PHOTOGRAPHIC 667 GID: BSXXXX

MANF: POLAROID

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00119.02	

TOXICITY

61388 FILM PHOTOGRAPHIC 7294 GID: BSXXXX

....NO TEST DATA AVAILABLE....

62141 FILM PHOTOGRAPHIC EN4 GID: BSXXXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.004		00.10	12.00	T MOD
X	1	025.9	014.3	0.004		01.49	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00019.99	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005659 3

63777 FILM PHOTOMICROGRAPHIC COLOR GID: BSXXXX
MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00020.95	

64262 FILM PHOTOSENSITIVE SCOTCHCAL GID: BPXXXX
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00010.20	

06323 FILM POLAROID 3000 LAND TY 107
MANF: POLAROID

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.005		00.95	06.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00015.82	

80185 FILM POLAROID 669 POLACOLOR ER INSTANT PACK GID: BSXXXX
MANF: POLAROID

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	127.11	

61981 FILM POLYCHROME/POLYESTER GID: BPCBXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.009		00.85	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.64	.02		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00018.94	

20894 FILM POLYESTER ALUMINIZED GID: BPCBFJ
MANF: MARTIN PROCESSING SPEC: MB0135-034T1
MCCORDI CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001		00.00	00.00	NONE
A	1	020.9	014.7	0.001			05.90	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.4E-6	.78	.11	.14	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

20439 FILM POLYETHYLENE GID: BPCSXX
MANF: POLY-AMERICA SPEC: MIL-B-81705T2 ST91P867-01
PROTECTIVE LINING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.005		00.97	12.00	T MOD
X	2	030.0	010.0	0.003		00.40	12.00	T MOD
X	1	030.0	010.0	0.003		01.90	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	8.0E-7	.24	.05		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
V	00002.26	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005660 T

06582 FILM POLYETHYLENE FR GID: BPCFXX
MANF: BRENTWOOD PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.004		00.19	12.00	T MOD
X	1	025.9	014.3	0.006		00.70	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.26	

TOXICITY

20662 FILM POLYETHYLENE8135-00-006-5962 GID: DTCCXX
MANF: GFE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.006		00.82	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	5.2E-6	.68	.08		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.54	

TOXICITY

20896 FILM POLYIMIDE ALUMINIZED GID: BPCDFJ
MANF: NATIONAL METALLIZING SPEC: MB0135-036T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.001			00.10	NONE
C	1	020.9	014.7	0.001		01.60	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.4E-6	1.26	.12	.96	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

64206 FILM POLYIMIDE/ALUMINUM/NOMEX/SCRIM GID: BPCDFJ
MANF: SHELDAHL SPEC: STM06910020202

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.010		00.30	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.3E-6	1.22	.00	1.02	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

20636 FILM POLYURETHANE 10 MIL GID: BPCQXX
MANF: DEERFIELD MFG CO SPEC: ST61P774-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.010		00.17	11.80	T MOD
X	1	025.9	014.3	0.010		00.50	11.80	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.9E-6	.90	.10		

ODOR

RT	RT	WEIGHT	CURE
A	A	00009.78	

TOXICITY

20635 FILM POLYURETHANE 5 MIL GID: BPCQXX
MANF: DEERFIELD MFG CO SPEC: ST61P774-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.005		00.32	11.80	T MOD
X	1	025.9	014.3	0.005		00.69	11.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	9.0E-6	.89	.08		

ODOR

RT	RT	WEIGHT	CURE
A	A	00009.53	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005661 1

20646 FILM POLYURETHANE GLOVE BLADDER GID: BPCQXX
MANF: ILC DOVER SPEC: ST65U091-03 ST65U091-06 ST65U092-05

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.015			03.70	MOD
X	2	033.0	014.3	0.015		00.54	12.00	T MOD
X	1	033.0	014.3	0.015		00.36	12.00	T MOD

FSC: RT FLUID NAME — No test data

OXYGEN COMP: RT TEST PRESS IMPACT TEMP THICK #REACT #TEST — No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	.30	.29		

ODOR: RT — A

TOXICITY: RT WEIGHT CURE — K 00020.00

20435 FILM POLYURETHANE HITUFF MP1880 GID: BPCQXX
MANF: STEVENS MOLDED PROD SPEC: ST61F087-03

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.012			05.50	MOD
X	2	025.9	014.3	0.030		00.20	12.00	T MOD
X	1	025.9	014.3	0.030		00.12	12.00	T MOD

FSC: RT FLUID NAME — No test data

OXYGEN COMP: RT TEST PRESS IMPACT TEMP THICK #REACT #TEST — No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.3E-6	.84	.12		

ODOR: RT — A

TOXICITY: RT WEIGHT CURE — V 00019.76

62936 FILM POLYURETHANE/CARBON LH86-13 GID: BPCQFO
MANF: PERVEL INDUSTRIES SPEC: SP-R-0022A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.003			09.00	NONE

FSC: RT FLUID NAME — No test data

OXYGEN COMP: RT TEST PRESS IMPACT TEMP THICK #REACT #TEST — No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.3E-6	.63	.18		

ODOR: RT — No test data

TOXICITY: RT WEIGHT CURE

63865 FILM RCA GID: BSXXXX
MANF: RCA

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR: RT

TOXICITY: RT WEIGHT CURE — A 01113.22

62480 FILM RISTON 730FR GID: BPCBCE
MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	5.2E-6	.44	.01		

ODOR: RT — No test data

TOXICITY: RT WEIGHT CURE

69856 FILM ROSCOLUX 51/SUPRISE PINK COLOR FILTER
MANF: ROSCO LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.002			00.70	NONE
X	1	030.0	010.0	0.002		1.50	12.00	T MOD

FSC: RT FLUID NAME — No test data

OXYGEN COMP: RT TEST PRESS IMPACT TEMP THICK #REACT #TEST — No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-6	.59	.09	.11	

ODOR: RT — A

TOXICITY: RT WEIGHT CURE — K 15.40

69821 FILM ROSCOLUX 88/LIGHT GREEN COLOR FILTER GID: BPCBXX
MANF: ROSCO LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.002			01.60	SMALL

FSC: RT FLUID NAME — No test data

OXYGEN COMP: RT TEST PRESS IMPACT TEMP THICK #REACT #TEST — No test data

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005662 3

69821 FILM ROSCOLUX 88/LIGHT GREEN COLOR FILTER (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.002		02.1	12.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-6	.35	.06	.09	

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	7.44	

20782 FILM RUCOTHANE CO-A5069 POLYURETHANE GID: BPCQXX

MANF: HOOKER CHEMICAL SPEC: ST65E1214-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.007		00.16	12.00	T MOD
X	1	025.9	014.3	0.007		00.45	12.00	T MOD

THERMAL VACUUM STABILITY

No test data

FSC

No test data

OXYGEN COMP

No test data

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.02	

61050 FILM RUCOTHANE CO-A5154 GID: BPCQXX

MANF: HOOKER CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	020.2	0.012		01.60	12.00	T MOD
X	1	100.0	020.2	0.012		01.91	12.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	1.27	.09	.46	

FSC

No test data

OXYGEN COMP

No test data

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00019.69	

62376 FILM RUCOTHANE CO-A769 POLYURETHANE GID: DODUXX

MANF: RUCO POLYMER SPEC: SVHS 10087

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.038			00.90	MOD
X	1	020.9	014.7	0.038			06.20	MOD
X	2	100.0	020.2	0.020		01.17	12.00	T MOD
X	1	100.0	020.2	0.020		01.46	12.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.2E-6	1.07	.19	.62	SEE TEST REPORT

FSC

No test data

OXYGEN COMP

No test data

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00022.27	8H-70F- 8H-150F-(AFTER DEMOLDING) 16H-150F-(AFTER THE LEACH CYCLE)

62712 FILM SAN GID: BPBOXX

MANF: DUPONT

FLAMMABILITY

No test data

FSC

RT	FLUID NAME
C	HYZE
C	MMH
X	MMH
X	N2O4

OXYGEN COMP

No test data

60802 FILM SARAN 18L GID: DUAEXX

MANF: DOW CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	012.3	0.001			03.60	NONE
A	1	023.8	014.5	0.002			02.00	NONE

FSC

No test data

OXYGEN COMP

No test data

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005663 5

60802 FILM SARAN 18L (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00011.46	

20333 FILM SARAN 8 CLEAR GID: BPAEXX

MANF: DOW CHEMICAL SPEC: ST92F129-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.001		00.00	00.00	NONE
A	1	023.8	014.5	0.001		00.00	00.00	NONE
B	2	025.9	014.3	0.001		00.00	00.00	NONE
B	1	025.9	014.3	0.001			06.30	NONE
A	1	030.0	009.0	0.001			01.60	NONE
I	2	100.0	020.2	0.001		00.84	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	50	72	120	0.001	00	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.8E-6	5.19	1.31		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00002.76	

61685 FILM SARAN PSD629/200GA CLEAR GID: COAEXX

MANF: DOW CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.002			00.30	NONE
B	1	025.9	014.3	0.002			07.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	7.0E-6	3.33	.29		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00012.20	

80294 FILM SCOTT CUSTOM GRADE GID: BPXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.500		0.47	12.00	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20438 FILM STABILENE DIAZO GID: BPCBXX

MANF: KEUFFEL & ESSER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.005			05.40	NONE
X	1	025.9	014.3	0.005		00.76	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.63	.11		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.08	

61445 FILM TEDLAR 200BG30 PVF GID: BPCJXX

MANF: DUPONT SPEC: MB0130-024

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.002			00.20	NONE
A	1	020.9	014.7	0.002			05.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.9E-6	.14	.01		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

62938 FILM TEDLAR 400 BS 30 WHITE GID: BPCJXX

MANF: DUPONT

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005664 7

62938 FILM TEDLAR 400 BS 30 WHITE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.004			06.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05153 FILM TEDLAR POLYVINYL FLUORIDE GID: BPCJXX

MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	X 00004.23	

TOXICITY

62937 FILM TEDLAR PVF 150 BLACK 30CC GID: BPCJXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001			05.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	00.14	00.00	00.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06615 FILM TEFLON FEP GID: BPBOXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001		00.00	00.00	NONE
X	1	025.9	014.3	0.001			01.00	MOD
A	1	030.0	010.4	0.001			02.70	NONE

FSC

RT	FLUID NAME
	HYZE
A	HYZE
C	HYZE
A	MMH
C	MMH
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.003	00	20

20884 FILM TEFLON FEP METALIED AL/AG SPEC: MB0125-064T1&2

MANF:

....NO TEST DATA AVAILABLE....

65414 FILM TEFLON FEP T160 GID: BPBOXX

MANF: H T L INDUSTRIES SPEC: AMS 3647

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.010	00	20

62503 FILM TEFLON GORTEX GID: BPCNXX

MANF: W L GORE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.024		00.50	11.20	T NONE
I	1	030.0	010.0	0.024		00.60	11.00	T NONE

FSC

RT	FLUID NAME
A	HYZE
C	HYZE
A	MMH
C	MMH
C	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65127 FILM TEFLON SILVER COATED GID: BPGQXX

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.005			03.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005665 9 ■

62217 FILM TEFLON TFE GID: BPCOXX
MANF: CADILLAC PLASTICS SPEC: ST92T837-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.005			02.80	MOD
X	1	033.0	014.3	0.005			03.60	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.01	.00		

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
A	A	00020.44	

60324 FILM TEMP SENSOR 110X
MANF: TELATEMP CORP
....NO TEST DATA AVAILABLE....

06047 FILM TFE LPW123 GRAPHITE FILL GID: BPCNGF
MANF: FLUOROCARBON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70	0.030	0	20
B	PNEU	1500		70	030	0	20

20458 FILM THERMOFILM 4500-5 GID: BPXXXX
MANF: THERMALLOY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.006			01.90	SMALL
C	1	033.0	014.3	0.006		00.17	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-7	.66	.04		

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
A	K	00020.11	

20399 FILM TUFTANE 310 POLYURETHANE GID: CHCQXX
MANF: B F GOODRICH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.021		00.25	12.00 T	MOD
X	1	025.9	014.3	0.021			09.30	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	.55	.17		

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
A	A	00019.95	

20308 FILM TUFTANE 410 POLYURETHANE GID: BPCQXX
MANF: B F GOODRICH SPEC: ST16T125-01 ST61T125-03

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.019		00.24	07.00	MOD
X	1	023.8	014.5	0.019		00.29	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.8E-7	1.35	.34		

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
A	X	00008.76	

60984 FILM TUFTANE T310 POLYURETHANE GID: BPCQXX
MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.022		00.18	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
A	K	00019.93	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005666 0

64015 FILM VERLCULOR VPS488 TYPE S GID: BSXXXX

MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00012.79	

TOXICITY

06377 FILM VINYL 3650G INK COATED P/S GID: BPCUHS

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.004	0.003		00.10	NONE
X	1	025.9	014.3	0.004	0.003		06.20	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.98	.14	.00	

ODOR

RT	RT	WEIGHT	CURE
A	A	00010.21	

TOXICITY

80268 FILM VINYL CLEAR UNPLASTICIZED WITH RUBBER RESIN ADHESIVE SYSTEM 14T-SS GID: BPXXXX

MANF: DEVON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.002	0.003		01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	18.763	

TOXICITY

06396 FILM VINYL COTTON TEXLE BACKED GID: BFCUFS

MANF: RECTICEL FOAM CORP
STEPHENSON & LAWYER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.5E-6	29.75	4.83		

ODOR

RT	RT	WEIGHT	CURE
	A	00008.94	

TOXICITY

61168 FILM VINYL GAUGE 8G GID: BPCUXX

MANF: GOSS PLASTIC FILM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.008			00.20	NONE
X	1	020.9	014.7	0.008		01.21	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06509 FILM WRIGHTLON 7400 GID: BPBYXX

MANF: GEMINI PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.003		00.69	05.20	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65343 FILM XRS1000 AGFA COLOR GID: BSXXXX

MANF: AGFA-GEVAERT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	25.53	

TOXICITY

63481 FILTER CARTRIDGE PTFE GID: FCXXXX

MANF: PALL ULTRAFINE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0			00.07	15.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005667 2

63887 FILTER MATERIAL HEPA GID: EXXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00042.20	

TOXICITY

64101 FILTER MATERIAL VERSAPOR 10000

MANF: GELMAN SCIENCES INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.9E-6	1.29	.01	1.07	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

20263 FILTER MEDIA BACTERIA GID: AAXXXX

MANF: AIRCRAFT POROUS MEDIA

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00006.24	

TOXICITY

61920 FILTER MEDIA TFE GORE-TEX GID: DICNXX

MANF: W L GORE SPEC: L-10942

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.004		00.27	12.00	T NONE
X	1	023.8	014.5	0.004		01.19	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	V	00002.93	

TOXICITY

06162 FILTER MICROFIBER GLASS/EPOXY

....NO TEST DATA AVAILABLE....

69925 FILTER NOMEX MEMBRANE

MANF: BRUNSWICK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE
X	MMH
X	N204

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80103 FILTER TYPE G THICKNESS G-0110

MANF: 3M CO
QPL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.142		00.40	10.90	LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	9.736	

TOXICITY

65480 FILTER WRATTEN GELATIN 29

MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00013.21	

TOXICITY

20229 FINISH SYSTEM F213B

MANF: IBM CORP SPEC: MIL-F-14072

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005668 4

20686 FLASHLIGHT

....NO TEST DATA AVAILABLE....

60997 FLASHLIGHT STREAMLITE 15 GID: FCXXXX

MANF: FUHRMAN DIVERSIFIED

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	014.5			00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00633.75	

61005 FLASHLIGHT STREAMLITE 20 GID: FCXXXX

MANF: STREAMLIGHT INC SPEC: SL-20

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0			00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00997.61	

62939 FLEX ELEMENT S/N-4 GID: FCXXXX

MANF: GOODYEAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.100		00.00	00.00	NONE
A	1	030.0	009.0	0.100		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64802 FLIGHT DATA FILE JCPK10 GID: BBGMAU

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.600		01.10	05.50	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64801 FLIGHT DATA FILE JCPK20 GID: BBGMAU

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.400		00.50	08.50	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65287 FLIGHT DATA FILE WITH BOOKS

MANF: NASA/MSFC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	06074.50	

20681 FLOSS DENTAL NYLON UNWAXED

....NO TEST DATA AVAILABLE....

64231 FLUIDTRONICS LIP SEAL

MANF: FLUIDTRONICS INC

....NO TEST DATA AVAILABLE....

02685 FLUOROCARBON RL-3540 GUM STOCK GID: DOEFXX

MANF: RAYBESTOS-MANHATTAN SPEC: MB0130-083

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.123		00.00	00.00	NONE
A	1	030.0	010.0	0.119		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005669 6

02685 FLUOROCARBON RL-3540 GUM STOCK (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	033.0	014.3	0.123			00.30	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.79	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.43	

64881 FLUOROCOMP #103 GID: DUCNIA

MANF: L N P CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	72	-220	0.121	0	20

05411 FLUOROGOLD TFE/GLASS 25% GID: AHCOFW

MANF: FLUOROCARBON CORP

SPEC: MIL-P-24074

MIL-P-24074T1GB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.068			00.20	NONE

FSC

RT	FLUID NAME
A	HYZE
A	MMH
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1050	72	550	0.060	3	109
X	PNEU	1050		550	0.060	5	49
B	MECH	14.7	72	-297	0.016	0	20
B	MECH	14.7	72	-297	0.047	0	40
B	MECH	14.7	72	-297	0.060	0	40
B	MECH	14.7	72	-297	0.063	0	60
B	MECH	14.7	72	-297	0.065	0	40
B	MECH	14.7	72	-297	0.090	0	20
B	PNEU	1500		70	0.090	0	20
B	MECH	250	72	275	0.016	0	20
B	PNEU	2500		65	0.063	0	20
B	MECH	255	72	275	0.047	0	20
B	MECH	255	72	275	0.051	0	20
B	PNEU	255		275	0.060	0	120
B	MECH	255	72	275	0.060	0	160
A	MECH	255	72	275	0.063	0	60
B	PNEU	255		275	0.193	0	20
X	PNEU	3000		65	0.063	2	29
X	PNEU	3500		65	0.063	2	19
B	MECH	400	72	275	0.038	0	20
B	MECH	400	72	275	0.056	0	20
B	PNEU	400		275	0.059	0	60
B	MECH	400	72	275	0.059	0	40
B	MECH	400	72	275	0.065	0	40
X	PNEU	4000		65	0.063	2	26
X	PNEU	4500		65	0.063	2	07
B	MECH	50	72	-297	0.090	0	20
B	PNEU	500		275	0.038	0	20
B	MECH	500	72	275	0.038	0	20
X	PNEU	5000		70	0.090	1	01
B	MECH	600	72	200	0.090	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.4E-7	.04	.00		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00210.97	

64969 FLUOROGOLD WITH GREEN PIGMENT GID: FIEFXX

MANF: FLUOROCARBON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	3000		65	0.063	0	20

MSFC-HDBK-527 REV F 9999942 0005670 2

Information Handling Services, 2000

64969 FLUOROGOLD WITH GREEN PIGMENT (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	3500		65	0.063	1	02
X	PNEU	4000		65	0.063	1	05
X	PNEU	4000		65	0.063	1	5
X	PNEU	4500		65	0.063	1	02

62838 FLUOROGRAY 5330-084-1774 GID: AHXXXX
MANF: GARLOCK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	72	-220	0.095	0	20

62840 FLUOROGRAY 5330-LNO-2628X GID: AHXXXX
MANF: GARLOCK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	72	-220	0.094	0	20

62835 FLUOROGRAY 5330-LNO-2638X GID: AHXXXX
MANF: GARLOCK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	72	-220	0.096	0	20

06088 FLUOROGREEN E-600 TFE/GLASS GID: DPCPXX
MANF: EPSCO INC
PEABODY DORE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYD

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	100	72	-297	0.098	0	20
A	MECH	400	72	-220	0.092	0	280
A	MECH	400	72	-297	0.092	0	220

05190 FLUOROLOY B TFE/CARBON/GRAPHITE GID: AHCNGF
MANF: FLUOROCARBON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.061			00.20	SMALL

FSC

RT	FLUID NAME
	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70	0.061	0	20
B	MECH	1500	72	70	0.061	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.4E-7	.02	.00		

ODOR TOXICITY

RT	RT	WEIGHT	CURE
A	K	00186.70	

05973 FLUOROLOY D GID: AHEFXX
MANF: FLUOROCARBON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.267		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR TOXICITY

RT	RT	WEIGHT	CURE
	A	00172.77	

05189 FLUOROLOY F TFE/CERAMIC GID: AHCNHO
MANF: FLUOROCARBON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.068			00.20	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1500	72	70	0.068	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005671 4

05189 FLUOROLOY F TFE/CERAMIC (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		70	0.068	01	20
X	PNEU	1500		70	0.068	1	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.4E-7	.04	.00		

ODOR TOXICITY

RT	RT	WEIGHT	CURE
A	K	00210.97	

05281 FLUOROLOY H TFE/BORON NITRATE GID: DPCNXX
MANF: FLUOROCARBON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.013			01.80	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70	0.012	0	20
Z	MECH	1500	72	70	0.012	2	34

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR TOXICITY

RT	RT	WEIGHT	CURE
A	A	00037.59	

63336 FLUOROLOY K GID: AHEFXX
MANF: FLUOROCARBON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	400	72	356	0.096	2	7

05194 FLUOROLOY KP TFE/ECONOL GID: AHCNMN
MANF: FLUOROCARBON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.027			00.30	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06567 FLUOROLOY S TFE/CD SE SULFIDE
MANF: FLUOROCARBON CORP
....NO TEST DATA AVAILABLE....

05174 FLUOROLOY SL TEFLON/GRAPHITE GID: AHCNGF
MANF: FLUOROCARBON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.169			00.20	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.175	0	20
B	MECH	1500	72	70	0.175	0	20
X	PNEU	1500		70	0.175	02	08
X	PNEU	1500		70	0.175	2	08

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.6E-7	.01	.01		

ODOR TOXICITY

RT	RT	WEIGHT	CURE
A	A	00020.50	

60343 FLUX
MANF: SPEC: MIL-F-14256
....NO TEST DATA AVAILABLE....

60732 FLUX HANDY TYPE B-1 GID: FLEFXX
MANF: HANDY & HARMAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	368	72	0.020	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005672 6

60205 FLUX SOLDER SPEC: MIL-F-20329 MIL-F-4995

MANF:

....NO TEST DATA AVAILABLE....

80292 FOAM INTERFLO HIGH MOLECULAR WEIGHT POLYETHYLENE HYDROPHOBIC FLAME RETARDANT GID: CAXXXX

MANF: CHROMAX CORP

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.250		0.01	11.50	T LARGE	No test data	No test data						
X	1	030.0	009.0	0.250		0.005	11.50	T LARGE								

05157 FOAM POLYURETHANE LAST-A-FOAM GID: CACQXX SPEC: MB0130-128T2

MANF: GENERAL PLASTICS

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.500			04.10	SMALL	No test data	No test data						

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.87	.02	.00	24H-248F-

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
No test data			

63389 FOAM PYRELL FOAM/IN METAL TOOLBOX GID: CAFKXX

MANF: ESA/ERNO

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.5	1.000			02.00	NONE	No test data	No test data						

85481 FOAM SOUNDFOAM "HT" POLYIMIDE GID: EXXXXX

MANF: SOUNDCOAT

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	1.000		00.13	03.75	NONE	No test data	No test data						

85479 FOAM SOUNDFOAM "HT" POLYIMIDE WITH NOMEX FABRIC FACING GID: CAXXXX

MANF: SOUNDCOAT

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	1.000		00.14	12.0	T LARGE	No test data	No test data						

85478 FOAM SOUNDFOAM 'M' POLYURETHANE GID: CAXXXX

MANF: SOUNDCOAT

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	1.000		00.32	12.0	T LARGE	No test data	No test data						

61275 FOOD RAT/MOUSE GID: CGXXXX SPEC: LMSC 5701803

MANF: ATCO
DOW CHEMICAL

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	A	00064.01	

61176 FUSE HOLDER GID: FCXXXX SPEC: MIL-F-19207B

MANF:

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	K	00015.98	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005673 8

60099 GAS HELIUM

....NO TEST DATA AVAILABLE....

60100 GAS NITROGEN

....NO TEST DATA AVAILABLE....

65212 GASKET 9-210-6B SILICONE GID: CHCKXX

MANF: AGC INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.9E-6	.30	.02	.05	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

80305 GASKET GYLON 1/16"

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	315	72	-290	0.0625	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.04	.04	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05245 GASKET MAIL ASBESTOS/RUBBER GID: DPXXXX

MANF:

SPEC: MIL-A-7021C1

....NO TEST DATA AVAILABLE....

05469 GASKET MATERIAL HASKON 8099 NOMEX/RUBBER SILICONE GID: CHCKBV

MANF: HASKON CORPORATION

SPEC: ZZ-R-765 CL 3A GR 30

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.088			00.10	NONE
A	1	023.8	014.5	0.088			01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05673 GASKET MATERIAL RUBBER SILICONE/NOMEX GID: DPCKXX

MANF: HADBAR

SPEC: MB0135-054
MIL-C-8193

MB0135-055
ZZ-R-765 CL 1B GR 50

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.1E-5	.24	.00		16H-480F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05828 GASKET MATERIAL X106 NOMEX/RUBBER GID: DPCKBV

MANF: ARROWHEAD PRODUCTS

SPEC: ZZ-R-765 CL 1B GR 50

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.3E-6	.31	.00		1.5H-300F- 16H-480F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

64126 GASKET MATERIAL/GOLD GID: CHXXXX

....NO TEST DATA AVAILABLE....

63869 GASKET MONEL/SILICONE DURO SOLID GID: CHXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	00023.70	

05697 GASKET POLASHEET SILICONE/MONEL GID: CHCKHI

MANF: METEX

SPEC: ZZ-R-765 CL 2 GR 50

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.060			02.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005674 T

05697 GASKET POLASHEET SILICONE/MONEL (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	023.8	014.5	0.060		00.09	12.00	T NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.25	.10	.00	

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

06240 GASKET RFI 01-0504 FERREX/SILI GID: CHCKXX

....NO TEST DATA AVAILABLE....

65483 GASKET RING FC-171 GID: CHXXXX

MANF: G S F PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME
A	HYZE

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

65482 GASKET RING FC-192 GID: CHXXXX

MANF: G S F PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME
A	HYZE

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

65481 GASKET RING FC-195 GID: CHXXXX

MANF: G S F PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME
A	HYZE

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

65484 GASKET RING GSF-1100 GID: CHXXXX

MANF: G S F PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME
A	HYZE

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

05940 GASKET SILICONE 7241/KEVLAR K120 GID: CHCKJH

MANF: ARROWHEAD PRODUCTS SPEC: ZZ-R-765 CL 3B GR 50

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.023			01.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	7.0E-7	.70	.02		8H-400F-

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

05334 GASKET SILICONE NOMEX HT 46-45 GID: CHBVCK

MANF: HADBAR SPEC: MB0135-054 ZZ-R-765

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.100			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.3E-6	.69	.15		

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

61955 GASKET SILICONE RUBBER GID: CHCKHD

MANF: ITT CANNON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.20	.00	.00	

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005675 1

06157 GASKET SILICONE/AL RFI 04-0102 GID: DVCKMA

MANF: SPEC: AMS 3302

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.025			01.40	NONE
B	1	033.0	014.3	0.025			11.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.36	.11		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.97	

62494 GASKET SILICONE/MONEL GID: CHCKXX

MANF: METEX SPEC: MIL-R-5847C2G50 QQ-N-281B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.029		00.33	10.90	T SMALL
I	1	030.0	009.0	0.039		00.03	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.6E-7	.36	.15		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.25	

20468 GASKET SIMRIT

....NO TEST DATA AVAILABLE....

85366 GASKET TECK SPAN P/N 48-09860 GID: CHXXXX

MANF: TEKNIT INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	81.9	

60627 GEL ELECTRODE DERMA-JEL GID: AXXXXX

MANF: PHYSIO CONTROL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00130.92	

01336 GERMICIDE PHENYLPHENOL PROPYL

....NO TEST DATA AVAILABLE....

20057 GLASS BOROSILICATE (INORGANIC) GID: FDIAGZ

MANF: CORNING GLASS WORKS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025		00.00	00.00	NONE
A	1	023.8	014.7	0.025		00.00	00.00	NONE
A	1	024.5	014.7	0.025		00.00	00.00	NONE
A	1	025.9	014.7	0.025		00.00	00.00	NONE
A	1	030.0	014.7	0.025		00.00	00.00	NONE
A	1	100.0	014.7	0.025		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	500		250	0.057	0	20
B	MECH	500	72	250	0.057	0	20
B	PNEU	500		70		0	20
B	MECH	500	72	70		0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.16	.06	.05	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00043.37	

05713 GLASS COMPRESSION (INORGANIC) GID: DOHOHO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025		00.00	00.00	NONE
A	1	023.8	014.7	0.025		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005676 3

05713 GLASS COMPRESSION (INORGANIC) (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.7	0.025		00.00	00.00	NONE
A	1	025.9	014.7	0.025		00.00	00.00	NONE
A	1	030.0	014.7	0.025		00.00	00.00	NONE
A	1	100.0	014.7	0.025		00.00	00.00	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.16	.06	.05	

ODOR

RT	WEIGHT	CURE

TOXICITY

RT	WEIGHT	CURE
A	00043.37	

20056 GLASS FLUORESCENT TUBE LAMP

MANF: WESTINGHOUSE

....NO TEST DATA AVAILABLE....

06543 GLASS OPTICAL (INORGANIC) GID: DOHOHO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025		00.00	00.00	NONE
A	1	023.8	014.7	0.025		00.00	00.00	NONE
A	1	024.5	014.7	0.025		00.00	00.00	NONE
A	1	025.9	014.7	0.025		00.00	00.00	NONE
A	1	030.0	014.7	0.025		00.00	00.00	NONE
A	1	100.0	014.7	0.025		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.16	.06	.05	

ODOR

RT	WEIGHT	CURE

TOXICITY

RT	WEIGHT	CURE
A	00043.37	

60237 GLASS PYREX GID: DOHOHO

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.7	0.025		00.00	00.00	NONE
A	1	024.5	014.7	0.025		00.00	00.00	NONE
A	1	025.9	014.7	0.025		00.00	00.00	NONE
A	1	030.0	014.7	0.025		00.00	00.00	NONE
A	1	100.0	014.7	0.025		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.16	.06	.05	

ODOR

RT	WEIGHT	CURE

TOXICITY

RT	WEIGHT	CURE
A	00043.37	

05617 GLASS TEMPERED(INORGANIC) GID: DOHOHO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025		00.00	00.00	NONE
A	1	023.8	014.7	0.025		00.00	00.00	NONE
A	1	024.5	014.7	0.025		00.00	00.00	NONE
A	1	025.9	014.7	0.025		00.00	00.00	NONE
A	1	030.0	014.7	0.025		00.00	00.00	NONE
A	1	100.0	014.7	0.025		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.16	.06	.05	

ODOR

RT	WEIGHT	CURE

TOXICITY

RT	WEIGHT	CURE
A	00043.37	

65345 GLOVE CLOTH NOMEX RTV 157 GREEN GID: BFBVXX

MANF: ILC DOVER

SPEC: MIL-C-83429T2C1 ST11N1945 CLOTH
ST34R1944 RTV

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005677 5

65345 GLOVE CLOTH NOMEX RTV 157 GREEN (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.070		00.09	09.30	SMALL
C	1	030.0	010.0	0.070		00.10	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00022.48	

60525 GLOVE COMFORT COTTON/POLYESTER GID: BFFSCB

MANF: ALPHA MILLS

....NO TEST DATA AVAILABLE....

62318 GLOVE COMFORT NYLON/ACRYLIC GID: FCBVAA

MANF: ILC DOVER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00015.06	

62336 GLOVE COMFORT NYLON/TRICOT GID: BFBVXX

MANF: FULTON FABRICS SPEC: STYLE N202

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	020.2	0.007		02.70	12.00	T NONE
X	1	100.0	020.2	0.007		04.60	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.4E-6	1.44	.09	1.20	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00009.64	

20522 GLOVE GS/FRP-2 GID: FGBVXX

MANF: MARIO PAPA & SONS SPEC: MIL-G-81188B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.080		00.20	12.60	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00078.08	

61058 GLOVE HANDLING ANIMAL 645 GID: XXCUXX

MANF: LITHGOW LABORATORY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00564.28	

63888 GLOVE INSULATED FES 3MF114AP GID: FGXXXX

MANF: STAR GLOVE & SAFETY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00241.40	

62418 GLOVE LATEX SOMAMED GID: DOACXX

MANF: INTERMEDCO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00016.64	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005678 7

20679 GLOVE PVC DISPOSABLE GID: EXAEXX
MANF: CURTIN MATHESON SCIENTIFIC INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.004		07.20	09.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.82	

60744 GLOVE RUBBER E-091 VITON GID: DOHDXX
MANF: NORTON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.010		00.50	09.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.55	

61012 GLOVE VINYL DERMA THIN GID: XXCUXX
MANF: AQM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00031.35	

60749 GLOVE VINYL DISPOSABLE 25165 GID: XXCUXX
MANF: EDMONT WILSON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00036.54	

61349 GLUE ELMERS GID: DPXXXX
MANF: BORDEN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.41	

61243 GOGGLES SUN 8465-530-4083 GID: EXXXXX
MANF: AMERICAN OPTICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00017.08	

61599 GRAPHITAR G36-295 GID: AHFOXX
MANF: U S GRAPHITE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.340		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.22	

05990 GRAPHITAR GRADE 14 GID: AHFOGF
MANF: U S GRAPHITE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.44	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005679 9

20146 GRAPHITAR GRADE 30A
MANF: U S GRAPHITE
....NO TEST DATA AVAILABLE....

60131 GRAPHITE ATJ
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

80015 GRAPHITE BAR/100% GRAFOIL GID: COXXXX
MANF: UNION CARBIDE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	12.4	72	-297	0.060	00	40
B	MECH	500	72	-297	0.060	00	40

64199 GRAPHITE FIBERITE HMF EPOXY GID: COGFBG
MANF: FIBERITE
SEE TEST NO.84-18204
....NO TEST DATA AVAILABLE....

05188 GRAPHITE G3418 GR GTB GRAFOIL GID: AHGFXX
MANF: UNION CARBIDE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.061		00.00	00.00	NONE

FSC

RT	FLUID NAME
	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1500	72	70	0.060	0	20
B	PNEU	1500		70	0.061	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.4E-6	.01	.00		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	K 00094.60	

64087 GRAPHITE GR-GTA/GRAFOIL
MANF: UNION CARBIDE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.160	0	20
B	MECH	300	72	-297	0.160	0	20

05465 GRAPHITE LUBE GID: CZGFXX
MANF: U S GRAPHITE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	A 00010.02	

60407 GREASE 880C & C
....NO TEST DATA AVAILABLE....

20246 GREASE AEROSHELL 17 GID: DBCBEJ
MANF: SHELL CHEMICAL SPEC: MIL-G-21164

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.010	0.009	00.03	12.00	T NONE
C	1	023.8	014.5	0.010	0.009	01.50	12.00	T NONE
C	2	030.0	010.0	0.010	0.010	00.05	12.00	T NONE
C	1	030.0	010.0	0.010	0.010	00.14	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.0E-7	79.05	53.34		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
	X 00003.90	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005680 5

20115 GREASE ANDOC C

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	53.76	50.92	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

20558 GREASE DC40 SILICONE GID: DBCKXX

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

06477 GREASE ELECTROMOLY 32 POLYGLY GID: DBXXXX

....NO TEST DATA AVAILABLE....

05641 GREASE HYDROCARBON GID: DBEKXX

MANF: MENASCO

SPEC: MIL-G-81322

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.010		00.03	09.80	NONE
C	1	023.8	014.5	0.010		01.42	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.6E-6	28.41	7.90		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00006.89	

20050 GREASE LUBRIPLATE 130A GID: DBXXXX

MANF: FISKE BROTHERS REFINING

....NO TEST DATA AVAILABLE....

20033 GREASE MOBIL 28 GID: DBEKXX

MANF: MOBIL OIL CORP

SPEC: MIL-G-81322B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	023.8	014.5	0.008	0.001		07.90	NONE
C	1	023.8	014.5	0.008	0.001	00.97	12.00	T NONE
C	1	025.9	014.3		0.003	00.00	00.00	NONE
C	1	025.9	014.3		0.003	01.38	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	0.0E-6	37.73	14.60		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00019.78	

60256 GREASE STERATE HYDROXYLIC CA12 GID: DBXXXX

MANF: TEXAS REFINERY CORP

....NO TEST DATA AVAILABLE. ..

61971 GROMMET NEOPRENE GID: BCHDXX

MANF: TRANSITRON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	.65	.20		24H-257F-0psia1E-4 TORR

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

64125 GUIDE LINER 1.5 STEM

MANF: VALTEK

....NO TEST DATA AVAILABLE....

64124 GUIDE LINER 2.5 STEM

MANF: VALTEK

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005681 7

61798 HALAR 300 CTFE/ETHYLENE

MANF: ALLIED CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	AMMONIA
A	HYZE
A	MMH
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05096 HALAR E-CTFE GID: DKEFBD

MANF: ALLIED CHEMICAL SPEC: MB0150-060

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.115			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.19	.00	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

20696 HAMMER BALLPEEN P/N BP-N-4A GID: FCXXXX

MANF: SNAP-ON-TOOLS SPEC: ST20T1013-06 ST20T1013-66

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	1.000		00.07	10.30	T SMALL
X	1	025.9	014.3	1.400			01.60	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00721.79	

60890 HANDLE DRIVER F40A GID: FCXXXX

MANF: SNAP-ON-TOOLS SPEC: ST20T1013-62

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00100.89	

60891 HANDLE DRIVER F50 GID: FCXXXX

MANF: SNAP-ON-TOOLS SPEC: ST20T1013-63

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00197.60	

20467 HARDENER AGOMET

....NO TEST DATA AVAILABLE....

62531 HARNESS AND CONNECTOR 26 AWG GID: ELHCXX

MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	4	023.8	014.5	0.124			00.00	NONE
X	1	023.8	014.5	0.124			01.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62533 HARNESS ASSEMBLY NOMEX BRAIDED 200 DENIER COVER GID: FFXXXX

MANF: HAMILTON STANDARD SPEC: SV771777/8/9

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	4	025.9	014.3	0.120			00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005682 9

80205 HARNESS PROTECTOR TEFLON GROMMET EDGING KG-023F GID: DDXXXX

MANF: KITAGAWA INDUSTRIES CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.050			00.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	22.147	

63416 HARNESS TENSOLITE ASSEMBLY 20AWC

MANF: TENSOLITE SPEC: STM-E300-1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	100.0	042.0	0.120		00.49	08.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65031 HEADBAND HEADSET MX2506/AIC GID: EXXXXX

MANF: NASA/JSC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	1.800		00.20	04.80	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00375.54	

63954 HEATER AUTOTRACE 10PTV1 18 AWG GID: BBXXXX

MANF: CHEMELEX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.109			02.70	MOD
X	1	033.0	014.3	0.120		00.08	07.10	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.20	.01	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00050.44	

60977 HEATER BELT AV14493 GID: DOCKXX

MANF: WALTERS ENG PROD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.85	

05676 HEATER BLANKET 372-4571 1-3M-4 GID: CKXXXX

....NO TEST DATA AVAILABLE....

05891 HEATER BLANKET 81873/840002G GID: CKXXXX

....NO TEST DATA AVAILABLE....

62509 HEATER STRIP HK607005A 24AWG GID: FCCDXX

MANF: MINCO PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.007			01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61184 HEATER STRIP HK607005B GID: FCCDXX

MANF: MINCO PRODUCTS

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	025.9	014.3	0.009	02.50	05.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005683 0

61184 HEATER STRIP HK607005B (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00009.41	

62508 HEATER STRIP/KAPTON 24 AWG GID: FCCDXX
MANF: MINCO PRODUCTS
SPEC: HR 608004B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	4	025.9	014.3	0.017			05.00	T NONE
C	1	025.9	014.3	0.017			01.20	.NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60897 HEATER WATLOW 02205580 GID: EZCKXX
MANF: WATLOW

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.2E-7	.29	.08		24H-350F-0psia10E-4

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

61286 HELMET ASTRONAUT GID: DDXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	02714.77	

60798 HELMET FLIGHT ANTI-G GID: FGXXXX
MANF: DAVID CLARK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	03486.30	

65026 HERBICIDE BOROSIL 4 SEE REPORT GID: AWXXXX
MANF: SIMPLOT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
S	HYZE
S	MMH
S	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60216 HEXANITRO STILBENE
....NO TEST DATA AVAILABLE....

63512 HOKE MULTIMITE 5-WAY BALL VALVE GID: FCBSXX
MANF: HOKE
....NO TEST DATA AVAILABLE....

61693 HOMALITE H-911 POLYESTER GID: FJCBXX
MANF: HOMALITE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.61	.01	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00020.07	

62789 HOSE AIR DUCT FLEXFLYTE L1 GID: DODPFV
MANF: AUTOMATION IND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.050			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00091.30	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005684 2

62790 HOSE AIR DUCT FLEXFLYTE L9 GID: DODPFV

MANF: AUTOMATION IND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.050			00.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00104.20	

60833 HOSE ASSEMBLY TITEFLEX R270-4 GID: EUBVXX

MANF: TITEFLEX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		025.9	014.3					NONE
A	1	030.0	009.0				01.20	NONE
A	1	033.0	014.3				00.80	NONE
X	1	100.0	020.2			01.59	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	7.9E-6	3.06	.08		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
V	00019.97	

20768 HOSE FEDFLEX SGG GID: EFXXXX

MANF: FEDERAL HOSE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	0.030		00.20	12.00	T SMALL
A	1	025.9	014.3	0.024			00.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00079.59	

63117 HOSE FLEX ASSEMBLY/FIRE SLEEVING GID: EXDPFV

MANF: TITEFLEX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3				01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

69866 HOSE FLEX DURAVENT U8 CLEAR GID: EGXXXX

MANF: DAYCO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.020		01.00	12.70	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	6.41	2.61	.22	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K		

62072 HOSE FLEX PTFE/CARBON FILLED GID: EGCOFO

MANF: RESISTOFLEX CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.066	3	15
X	PNEU	2000		70	0.066	2	02
X	PNEU	3000		70	0.066	1	04
B	PNEU	500		70	0.066	0	20
C	MECH	6000	60	70	0.065	00	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005685 4

69876 HOSE FLEX R19840X-032L GID: EGXXXX
MANF: RESISTOFLEX CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.060			00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.01	.02	.01	

ODOR

RT	RT	WEIGHT	CURE
	K		

TOXICITY

65190 HOSE FLEX RTV 630 GID: EGXXXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.300			02.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60822 HOSE FLEX SILFAB-1 SIL/GL/FAB GID: EGCKXX
MANF: FLEXFAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.028			03.50	SMALL
I	1	030.0	009.0	0.028		00.10	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00071.81	

TOXICITY

60821 HOSE FLEX SILFAB-2 SIL/GL/FAB GID: EGCKXX
MANF: FLEXFAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	0.040		00.10	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00080.90	

TOXICITY

62397 HOSE FLEX TEFLON/1% CARBON GID: EGCOMJ
MANF: HAMILTON STANDARD
SPEC: SED38106631

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70		0	50
B	PNEU	3000		70		0	50
B	PNEU	3750		70		0	50
B	PNEU	5000		70		0	50
B	PNEU	6000		70		0	50

60818 HOSE FLEX TURBOFAB FLUOROSILICONE GID: EGEGXX
MANF: FLEXFAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.055		00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00138.30	

TOXICITY

60144 HOSE FLUOROFLEX-T GID: EFCNXY
MANF: RESISTOFLEX CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005686 6

60854 HOSE FLUOROFLEX-T T1000 GID: EFCNXX

MANF: RESISTOFLEX CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	70	0.064	1	60
Z	MECH	1500	72	70	0.064	3	45
Z	MECH	2000	72	70	0.064	02	12
B	MECH	500	72	70	0.064	0	40
C	MECH	6000	35	70	0.064	0	20

61280 HOSE NYTRON PRESSURE GID: EFXXXX

MANF: IMPERIAL EASTMAN

SPEC: SAE 100R7

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	.068	4	09
X	PNEU	1000		70	0.068	4	09
X	PNEU	1500		70	.068	1	01
X	PNEU	1500		70	0.068	1	01
B	PNEU	500		70	.068	0	40
B	PNEU	500		70	0.068	0	40
B	PNEU	750		70		0	20
X	PNEU	950		70		1	49

62289 HOSE LINER FLEX TFE/25% CARBON GID: CKCNFO

MANF: TITEFLEX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME
A	HYZE
A	MMH
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

62553 HOSE LINER PTFE GID: EFCOXX

MANF: ATLAS CORP
RESISTOFLEX CO
TITEFLEX

SPEC: MIL-H-27267

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70	0.060	0	20
X	PNEU	1500		70	0.060	1	16
X	PNEU	2000		70	0.060	1	20
X	PNEU	2500		70	0.060	1	09
X	PNEU	3000		70	0.060	01	03
B	MECH	400	72	-220	0.053	00	460

62907 HOSE LINER TEFLON CONDUCTIVE GID: EFCOXX

MANF: ATLAS CORP

SPEC: RD-2974

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	72	-220	0.060	0	100
B	MECH	400	72	-297	0.060	0	80

61932 HOSE LINER/R762-8 HOSE GID: CKCPXX

MANF: RESISTOFLEX CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME
A	AMMONIA
A	HYZE

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	.049	2	14
X	PNEU	1000		70	0.049	2	14

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005687 8

61932 HOSE LINER/R762-8 HOSE (cont)

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
									A	MMH	X	PNEU	2000		70	0.049	2	09
									A	N2O4	X	PNEU	3000		70	0.049	2	09
											X	PNEU	4000		70	.049	2	12
											X	PNEU	4000		70	0.049	2	12
											B	PNEU	500		70	.049	0	20
											B	PNEU	500		70	0.049	0	20
											X	PNEU	5000		70	0.049	2	13
											X	PNEU	6000		70	0.049	1	02

65110 HOSE NEOFAB-2 FLEX GID: EFDBGD
MANF: FLEXFAB

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	024.5	014.5	0.024			04.70	SMALL	No test data		No test data							
I	1	030.0	009.0	0.024		00.30	12.00	T SMALL										

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	00074.47	

63118 HOSE NEOPRENE CWC GID: EFDBXX
MANF: FLEXAUST

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	024.5	014.3	1.125			01.50	NONE	No test data		No test data							
A	1	025.9	014.3	0.050			03.00	NONE										

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							X	00100.00	

60996 HOSE NEOPRENE P/N 801005 GID: EFDBXX
MANF: AMERICAN CLEANING

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.200		00.00	00.00	NONE	No test data		No test data							

63120 HOSE NEOPRENE TYPE A GID: DODBXX
MANF: GATES MFG CO

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	145.0			00.40	04.00	T SMALL	No test data		No test data							

60260 HOSE NYLON COIL N344
MANF: COILHOSE PNEUMATICS
....NO TEST DATA AVAILABLE....

62438 HOSE NYLON/TEFLON R531-4 GID: EFBVCN
MANF: RESISTOFLEX CO SPEC: ASTM D1457

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.050		00.07	08.00	T MOD	No test data		No test data							

61882 HOSE PARFLEX 540N/POLYURETHANE GID: EGBSCQ
MANF: PARKER HANNIFIN SPEC: SAE 100R3

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		X	PNEU	500		72		2	14

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005688 T

61882 HOSE PARFLEX 540H/POLYURETHANE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	500	10	72		01	20
X	PNEU	600		72		01	11

61881 HOSE PARFLEX 558H/POLYESTER GID: EGCBGU
MANF: PARKER HANNIFIN
SPEC: SAE 100R7

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70		01	02
X	MECH	1000	10	70		01	01
X	PNEU	500		70		01	14
X	MECH	500	10	70		01	03
X	PNEU	600		70		01	03

62034 HOSE PLASTIC/SILICONE RUBBER GID: EGBYDP
MANF: HOOVER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3			00.16	42.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00428.60	

80149 HOSE PLSS FLEX TEFLON LINED GID: EXXXXX
MANF: TITEFLEX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
S							

65197 HOSE R267/410 SERIES GID: EGXXXX
MANF: TITEFLEX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00166.13	

64200 HOSE R502-16Z TEFLON GID: EGXXXX
MANF: RESISTOFLEX CO
SEE TEST NO.85-18390
....NO TEST DATA AVAILABLE....

64202 HOSE R502-6 TEFLON GID: EGXXXX
MANF: RESISTOFLEX CO
SEE TEST NO.85-18394
....NO TEST DATA AVAILABLE....

64302 HOSE R502-8 TEFLON GID: EGXXXX
MANF: RESISTOFLEX CO
SEE TEST NO.18392
....NO TEST DATA AVAILABLE....

20649 HOSE REDAR A111331-1 VITON B GID: EFHDXX
MANF: R E DARLING
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005689 1

Information Handling Services, 2000

62478 HOSE REDAR A11200 SILICONE/PBI GID: EFCKBV

MANF: R E DARLING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.025		00.00	00.00	NONE
A	1	030.0	010.4	0.025		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61562 HOSE REDAR SI644-01 SILICONE GID: EGCKXX

MANF: R E DARLING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3				01.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00276.44	

63121 HOSE RTV SILICONE GID: EFDPXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	024.5	014.3				06.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20557 HOSE SILICONE MS70G31 GID: EKCKXX

MANF: MOXNESS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.076		00.08	12.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.46	.46		24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.09	

65351 HOSE SILICONE PUROSIL 70-087 GID: DOCKCB

MANF: BOYD INDUS RUBBER SPEC: MIL-H-62217-1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.210		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00027.66	

65350 HOSE SILICONE PUROSIL 80-100 GID: DOCKCB

MANF: BOYD INDUS RUBBER SPEC: MIL-H-62217-1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.230		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00023.22	

62437 HOSE SILICONE/PBI POS BREATHER GID: EFCKHE

MANF: CELANESE SPEC: SV777202-1
HAMILTON STANDARD
MOXNESS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.325		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.1E-5	8.29	.06	8.23	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00296.29	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005690 8

05854 HOSE TEFLON 1% CONDUCT ADDITIX GID: EFCOXX

....NO TEST DATA AVAILABLE....

69845 HOSE TEFLON LINER (PROTION FROM HYDROCARBON SAMPLE LINE) GID: EFXXXX

MANF: NASA/KSC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.01	.02	.01	

ODOR TOXICITY

RT	RT WEIGHT	CURE
No test data		

60987 HOSE TEFLON PTFE R735 GID: CKCPXX

MANF: RESISTOFLEX CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	100		70	.014	0	20
X	PNEU	1000		70	.060	1	04
X	PNEU	1000		70	0.060	1	04
X	PNEU	1500		70	0.060	1	02
X	PNEU	2000		70	0.060	1	02
X	PNEU	2500		70	0.055	1	04
X	PNEU	3000		70	.050	1	01
X	PNEU	3000		70	0.050	1	01
X	PNEU	4000		70	0.056	01	07
X	PNEU	4500		70	0.054	1	01
X	PNEU	5000		70	0.054	1	03
X	PNEU	5000		70	0.054	1	08
X	PNEU	6000		70	.054	1	03
X	PNEU	6000		70	0.042	1	03

60728 HOSE TEFLON PTFE R765 GID: EFCNXX

MANF: RESISTOFLEX CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	.047	4	50
X	PNEU	1000		70	0.047	4	50
X	PNEU	1500		70	0.047	4	76
X	PNEU	2000		70	0.047	5	74
X	PNEU	2500		70	0.050	7	51
X	PNEU	3000		70	.050	7	32
X	PNEU	3000		70	0.050	7	32
X	PNEU	3500		70	0.050	3	20
X	PNEU	4000		70	0.050	4	17
X	PNEU	4500		70	0.050	2	10
B	PNEU	500		70	.047	0	20
B	PNEU	500		70	0.047	0	20
X	PNEU	5000		70	0.050	2	15
X	PNEU	5500		70	0.049	1	02
X	PNEU	6000		70	0.049	1	09
X	PNEU	6500		70	.049	2	05
X	PNEU	6500		70	0.049	2	05

61031 HOSE TEFLON T6C GID: EFCOXX

MANF: RESISTOFLEX CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	PNEU	2000		70	0.035	0	06
B	PNEU	3000		70	0.035	0	20
X	PNEU	3500		70	0.035	1	11

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005691 T

61031 HOSE TEFLON T6C (cont)

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
											B	PNEU	4000		70	0.050	0	40
											X	PNEU	4500		70	0.050	2	33
											X	PNEU	5000		70	0.050	4	27
											X	PNEU	5500		70	0.050	3	22
											X	PNEU	6000		70	0.050	3	13

61820 HOSE TEFLON TFE R736 GID: EFCNXX
MANF: RESISTOFLEX CO

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		I	PNEU	1000		70	.250	0	08
											I	PNEU	1000		70	0.250	0	08
											X	PNEU	1500		70	0.500	2	25
											X	PNEU	2000		70	0.250	2	06
											B	PNEU	2500		70	.250	0	20
											B	PNEU	2500		70	0.500	0	20
											B	PNEU	3000		70		0	22
											X	PNEU	3000		70	0.500	1	07
											B	PNEU	3500		70		0	40

65271 HOSE TEFLON WITH STEEL GID: EGCOXX
MANF: AEROQUIP

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	00380.43	

69874 HOSE TEMPFLEX PLUS BLACK GID: EGXXXX
MANF: DAYCO CORP

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	030.0	010.0	0.020		00.60	12.00	T NONE	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	4.0E-6	.58	.06	.30			K		

62052 HOSE TFE/CARBON FILLED GID: EGBDXX
MANF: ATLAS CORP

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									A	HYZE	No test data							

65331 HOSE TITEFLEX CONDUCTIVE GID: EFCNXX
MANF: TITEFLEX

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		I	MECH	400	10	-297	0.687	0	40

64845 HOSE URINAL SILICONE RUBBER/WIRE GID: EGDPXX
MANF: R E DARLING SPEC: ZZ-R-765

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.175		00.00	00.00	NONE	No test data		No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005692 1

62022 HOSE WAVA SILICONE/NOMEX GID: EGCKBV

MANF: R E DARLING

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	$REACT	#TEST
A	1	025.9	014.3	1.300			01.30	NONE	No test data		No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY	
RT	RT	WEIGHT	CURE
	A	00384.23	

63124 ID PLATE PHOTO/MACBOND 1B1160 GID: CNXXXX

MANF: MATAC

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.5	0.015			02.10	NONE	No test data		No test data							

80052 IGNITION HAZARD PROOFING OF VLS ENVIRONMENTAL SAMPLERS

MANF: WSTF

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									S		No test data							

60145 IGNTN GRANULES-BORON PTSM NITR

MANF: CELESCO

....NO TEST DATA AVAILABLE....

20187 IMPREGNANT BRAZING

MANF: SPEC: MIL-I-6869

....NO TEST DATA AVAILABLE....

05860 INK 17 GID: APXXXX

....NO TEST DATA AVAILABLE....

61913 INK 4025/JCP K10 YELLOW GID: APXXXX

MANF: A W FABER

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY	
RT	RT	WEIGHT	CURE
A	A	00023.22	

61914 INK 4085/JCP K10 RED GID: APXXXX

MANF: A W FABER

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY	
RT	RT	WEIGHT	CURE
A	A	00022.92	

60193 INK 40M12864 BLACK GID: APXXXX

MANF: SPEC: MSFC STD-383

....NO TEST DATA AVAILABLE....

64312 INK 41 BLACK PASTE GID: APXXXX

MANF: INDEPENDENT INK

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	2	024.5	014.3	0.002		00.00	00.00	NONE	No test data		No test data							
A	1	024.5	014.3	0.002		00.40	05.80	NONE										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	2.2E-6	8.56	.92	.38	168H-70F-

ODOR	TOXICITY	
RT	RT	WEIGHT	CURE
No test data			

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005693 3

61915 INK 4115/JCP K10 VIOLET GID: APXXXX
MANF: A W FABER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00023.39	

TOXICITY

61917 INK 4145/JCP K10 BLUE GID: APXXXX
MANF: A W FABER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	V	00023.00	

TOXICITY

64306 INK 42-11FD MARKING BLACK GID: APXXXX
MANF: ESSELTE PENDAFLEX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	025.9	014.3	0.001		00.00	00.00	NONE
A	1	025.9	014.3	0.001		02.70	04.86	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.0E-6	8.40	.00	.27	

ODOR

RT	RT	WEIGHT	CURE
X	X	00004.36	168H-70F-

TOXICITY

61912 INK 4205/JCP K10 GREEN GID: APXXXX
MANF: A W FABER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00023.19	

TOXICITY

61911 INK 4295/JCP K10 BROWN GID: APXXXX
MANF: A W FABER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00023.34	

TOXICITY

61916 INK 4415/JCP K10 BLACK GID: APXXXX
MANF: A W FABER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	V	00023.34	

TOXICITY

80177 INK 51022 GREEN/K10 PAPER GID: DPXXXX
MANF: VAN BUREN INK CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	X	8.232	168H-75F-12.4psia

TOXICITY

80166 INK 57377 YELLOW/K10 PAPER GID: APXXXX
MANF: MIDLAND COLOR

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	X	7.962	168H-75F-12.4psia

TOXICITY

80270 INK 61121 BROWN GID: APXXXX
MANF: MIDLAND COLOR

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	X	7.789	168H-75F-12.4psia

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005694 5

00010 INK 73X GID: APXXXX
MANF: INDEPENDENT INK — SPEC: MB0190-003T1 — TT-I-1795T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002			01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	62.20	.90	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
B	00005.05	168H-70F- 24H-150F-

65106 INK 8447 BLACK GID: APCKXX
MANF: MARKEM — SPEC: MC621-0043

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002	0.003		00.30	NONE
A	1	030.0	010.0	0.003	0.003		00.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00022.61	768H-70F- 24H-150F-

05849 INK 944 GID: APXXXX
....NO TEST DATA AVAILABLE....

05490 INK 977-9 GID: APXXXX
MANF: STATE STAMP INK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.6E-6	19.03	.22		24H-70F- 24H-150F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00002.65	24H-70F- 24H-150F-

69967 INK 9900 ON LEXAN GID: CNXXXX
MANF: COLONIAL PRINTING/GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	032.0	010.0	0.012		0.8	08.50	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	21.727	

61840 INK A-M CS174C/JCP K10 BLACK GID: APXXXX
MANF: BRADEN STUPHIN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
V	00022.99	

61839 INK B5749/JCP K10 LITHO-ITEK GID: APXXXX
MANF: UNIVERSAL PRINTING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00022.65	

20180 INK BEE R222/T266 THINNER GID: APXXXX
MANF: BEE CHEMICAL CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00001.04	24H-150F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005695 7

20665 INK BIC AF69 GID: APXXXX
MANF: BIC INC SPEC: ST80S756-01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.4E-6	19.59	1.33		168H-70F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	X	00000.80	168H-70F-

20631 INK BIC MARKING PM DELUX GID: APXXXX
MANF: BIC INC SPEC: ILC ST20P623-05 ILC ST20P623-06

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	B	00000.09	168H-70F-

20875 INK BLADDER MARKING URETHANE GID: APCQXX
MANF: CARDINAL PAINT CO
RUCO POLYMER
SPEC: SVHS 10077

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	100.0	020.2	0.018			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	20.39	13.21	.28	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	A	00009.97	

62421 INK CANON HP270F/JCP E20PAPER GID: APXXXX
MANF: CANNON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	K	00022.62	

63125 INK CAT-L-INK 50-100R/20 GID: APBGXX
MANF: HYSOL/DEXTER SPEC: MIL-I-43553

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	0.009		00.54	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.62	.01	.00	.5H-70F-
					.5H-280F-
					4H-300F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	X	00017.32	

80061 INK CAT-L-INK 50-110/20 GID: APXXXX
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	12.35	.03		3H-176F-
					336H-70F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

69962 INK CAT-L-INK 50-403R/20
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	12.24	.11	.13	1H-150F-
					48H-167F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

80060 INK CAT-L-INK 50-508R/20 GID: APXXXX
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	13.89	.02		3H-176F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005696 9

80060 INK CAT-L-INK 50-508R/20 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					332H-70F-

ODOR

RT	RT WEIGHT	CURE

TOXICITY

64014 INK CAT-L-INK 50-70 EPOXY GID: APBGXX

MANF: HYSOL/DEXTER SPEC: MIL-I-43553

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.0E-6	8.33	.04	.64	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63126 INK CAT-L-INK 50-700/1 GID: APXXXX

MANF: HYSOL/DEXTER SPEC: MIL-I-43553

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.013	0.001	01.10	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	26.24	.11	.00	2H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63127 INK CAT-L-INK 50-700R/20 GID: APBGXX

MANF: HYSOL/DEXTER SPEC: MIL-I-43553

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.007		00.68	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	19.20	.01		3H-131F-
					504H-70F-

ODOR

RT	RT WEIGHT	CURE
X	00020.00	120H-70F-

TOXICITY

61449 INK CAT-L-INK 50-700R/9 GID: APXXXX

MANF: HYSOL/DEXTER SPEC: MBO190-003T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002		00.33	03.10	SMALL
I	1	030.0	010.0	0.005		00.20	12.00 T	SMALL
A	1	030.0	010.0	0.002		00.41	04.70	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	9.41	.00	8.42	8H-149F-

ODOR

RT	RT WEIGHT	CURE
X	00024.45	.5H-70F-

TOXICITY

69960 INK CAT-L-INK 50-710/20

MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	6.43	.07	.39	1H-150F-14.7psia
					48H-167F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61007 INK CAT-L-INK 50-770 GID: APBGXX

MANF: HYSOL/DEXTER SPEC: EPS 37-094

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	26.24	.11	.00	3H-70F-

ODOR

RT	RT WEIGHT	CURE
X	00015.54	24H-70F-

TOXICITY

20126 INK CERAMIC WITH IRON OXIDE INORGANIC GID: APHOXX

MANF: COLORTONE

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005697 0

06019 INK COLITHO 0691-19003/JCP E20 GID: APGMXX

MANF: GSA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	023.8	014.5	0.004		00.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00006.56	

20157 INK DEUTSCH DPS CL 1,3,4,5 GID: APXXXX

MANF: DEUTSCH

....NO TEST DATA AVAILABLE....

05902 INK DEUTSCH DPS I140-01 MARKNG GID: APXXXX

MANF: DEUTSCH

....NO TEST DATA AVAILABLE....

20085 INK DEUTSCH DPS147 GID: APXXXX

MANF: DEUTSCH

....NO TEST DATA AVAILABLE....

20084 INK DEUTSCH DPS300 GID: APXXXX

MANF: DEUTSCH

....NO TEST DATA AVAILABLE....

61694 INK DICK-B-4020C ON JCP E20 GID: APGMXX

MANF: GSA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	023.8	014.5	0.004		00.10	10.50	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00006.76	

62196 INK DRY 9200/JCP E20 PAPER GID: DIAUXX

MANF: XEROX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.004		00.13	10.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00005.47	

62197 INK DRY 9200/JCP K10 PAPER GID: DIAUXX

MANF: XEROX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.009		00.07	10.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00011.35	

20773 INK DURAGRAPH B20082 AL RED GID: APXXXX

MANF: DURAGRAPH SYSTEMS

SPEC: SV772104-1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.1E-6	.23	.01	.11	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00172.80	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005698 2

62262 INK DYNACURE LETTERING GID: APXXXX
MANF: DYNACHEM
THIOKOL
SPEC: HMS 15-2004

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	1.45	.00		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05653 INK EPOXY GID: APBGXX
....NO TEST DATA AVAILABLE....

20447 INK EPOXY 128-45C BLACK GID: APBGXX
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

06340 INK EPOXY BASE BLK BPS19-00-1 GID: APXXXX
....NO TEST DATA AVAILABLE....

20203 INK F100 BLACK GID: APXXXX
MANF: ORGANIC PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.2E-6	16.64	.00		24H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
X	1.791	504H-70F-

TOXICITY

80092 INK F30 BLACK
MANF: BEROL CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.04	.01	.00	24H-149F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

69993 INK F600 MYLAR BLACK
MANF: ORGANIC PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	033.0	010.0	0.001	0.003		05.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	19.05	.04	.95	169H-70F-

ODOR

RT	RT WEIGHT	CURE
A	X 5.287	

TOXICITY

05903 INK FRS MARKING 7224 GID: APXXXX
MANF: MARKEM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.59	.07	1.32	2H-248F- .05H-446F-

ODOR

RT	RT WEIGHT	CURE
A	X 00005.80	24H-150F-

TOXICITY

80173 INK HIGGINS BLACK MAGIC WATERPROOF INDIA 4465 GID: APXXXX
MANF: FABER CASTELL CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	X 3.272	24H-75F-12psia

TOXICITY

20507 INK INDELIBLE MARKING GID: APXXXX
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005699 4

20515 INK JUSTRITE INDELIBLE GID: APXXXX
MANF: LOUIS MELIND CO
SPEC: ST11N701-01 ST80M893-01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.8E-6	2.96	.00		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00004.59	

06551 INK K46 BLACK ON KYNAR/VITON GID: APXXXX
....NO TEST DATA AVAILABLE....

05996 INK K486 HOT STAMP BLUE-BLACK GID: AKXXXX
MANF:
SPEC: MIL-M-81594T4
....NO TEST DATA AVAILABLE....

62443 INK KODAK 250/JCP E20 PAPER GID: APXXXX
MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00022.85	

20493 INK KP402 URETHANE WHITE T102
MANF: WILMINGTON CHEM CO
....NO TEST DATA AVAILABLE....

20025 INK KX425 BLACK GID: APXXXX
MANF: DEKEM CO
....NO TEST DATA AVAILABLE....

05901 INK L-O-M SERIES MARKING GID: APXXXX
MANF: HYSOL/DEXTER
P1111/CAT33-P0724

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00003.25	168H-70F- 24H-150F-

20488 INK LUMOCOLOR 317 GID: APXXXX
MANF: GFE
STAEDTLER
....NO TEST DATA AVAILABLE....

20190 INK M219 VULCAN BLACK GID: APXXXX
MANF: J A MATTHEWS CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		00.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.4E-6	28.56	.01		24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00002.06	24H-70F- 24H-150F-

69857 INK MARKEM 6887 BLACK AND 112XD THINNER
MANF: MARKEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.002	0.003		02.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	7.56	120H-70F-

MSFC-HDBK-527 REV F 9999942 0005700 7

Information Handling Services, 2000

05551 INK MARKEM 7132H GID: APXXXX
MANF: MARKEM
....NO TEST DATA AVAILABLE....

05678 INK MARKEM 7254 P/K BLACK GID: APXXXX
MANF: MARKEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	030.0	010.0	0.002	0.003		00.00	NONE
B	1	030.0	010.0	0.002	0.003	0.80	07.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.6E-7	9.34	.04		1H-70F- 24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	22.643	1H-70F-

05865 INK MARKEM 7907 SILK SCREEN GID: AGXXXX
MANF: MARKEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003		02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	13.28	.01		24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00004.75	24H-70F- 24H-150F-

05888 INK MARKEM 8855 WHITE GID: ATXXXX
MANF: MARKEM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00011.24	168H-70F- 24H-150F-

64842 INK MARKER PEN 2500/JCP E20 GID: APXXXX
MANF: SANFORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	025.9	014.3	0.004		00.19	10.50	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00044.40	

64841 INK MARKER PEN 2500/PAPER GID: APXXXX
MANF: SANFORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00044.40	

05687 INK MARKING 1448 BLACK GID: APXXXX
....NO TEST DATA AVAILABLE....

20349 INK MARKING 44 GID: APXXXX
MANF: PHILLIPS CHEMICAL SPEC: SP-R-0022A ST805624-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.140	0.003		01.80	NONE
A	1	030.0	009.0	0.002			15.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005701 9

20349 INK MARKING 44 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	10.53	2.14	.00	24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00058.66	168H-70F-

85407 INK MARKING A423-66 BASE T252-66 CONVERTER

MANF: KOPPERS CO SPEC: MMS-K010

....NO TEST DATA AVAILABLE....

20098 INK MARKING ALKYD BLACK GID: APAOXX

MANF: INK STAMPING CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.53	5.10	.00	SEE TEST REPORT

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00007.50	25H-70F- 24H-150F-

61713 INK MARKING BLACK GID: APXXXX

MANF: METRON OPTICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.4E-7	4.54	.21		168H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00000.73	168H-70F- 24H-150F-

61712 INK MARKING BLUE GID: APXXXX

MANF: METRON OPTICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.4E-7	5.47	.40		168H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00000.86	168H-70F- 24H-150F-

05593 INK MARKING FRS6811 BLACK GID: APXXXX

MANF: MARKEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.006	0.003		04.10	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.3E-6	11.67	2.28		168H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00004.88	24H-70F- 24H-150F-

06215 INK MARKING FRSI SILICONE GID: APCKXX

MANF: SPEC: MA0604-301

....NO TEST DATA AVAILABLE....

05899 INK MARKING K36 BLACK GID: APBSXX

MANF: KINGSLEY MACHINE CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.2E-6	29.74	.32	3.99	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00019.92	

69986 INK MARKING K480 BLUE/BLACK FOIL

MANF: KINGSLEY MACHINE CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.002		00.30	12.00	T NONE
X	1	030.0	010.0	0.002		03.70	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0005702 0

Information Handling Services, 2000

69986 INK MARKING K480 BLUE/BLACK FOIL (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.0E-6	16.70	.03	5.68	

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE
A	10.245	

60146 INK MARKING PARACHUTES GID: APXXXX

MANF:

SPEC: MIL-I-6903

....NO TEST DATA AVAILABLE....

06119 INK MARKING RADIOGRAPH 580005 GID: APXXXX

MANF: KEUFFEL & ESSER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	5.83	.03	3.68	24H-75F- 1056H-75F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	0.935	24H-75F- 1056H-75F-

61711 INK MARKING RED GID: APXXXX

MANF: METRON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.4E-7	3.60	.66		168H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00000.76	168H-70F- 24H-150F-

06589 INK MARKING SPECIAL 13

MANF: MAR-KING

....NO TEST DATA AVAILABLE....

60127 INK MARKING STENCIL

MANF: AQM

SPEC: TT-I-1795T1

....NO TEST DATA AVAILABLE....

85387 INK MARKING UVEXS 105E BLACK

MANF: UVEXS CORP

SPEC: P/N 9006116

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	14.50	0.001	0.003	0.22	6.70	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85398 INK MARKING WE44 RED

MANF: SUN CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	22.265	

61714 INK MARKING WHITE GID: APXXXX

MANF: METRON OPTICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.4E-7	2.32	.08		168H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00000.55	168H-70F- 24H-150F-

20727 INK NAZDAR ER112 EPOXY GID: APBGXX

MANF: NAZ DAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.006	0.003		02.60	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005703 2

20727 INK MAZDAR ER112 EPOXY (cont)

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	030.0	009.0	0.006			06.00	SMALL									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
I	2.0E-6	5.96	.00		24H-70F- 24H-150F-	A	B	00019.52	24H-70F- 24H-150F-

60377 INK MOC GID: APXXXX
MANF: AQM SPEC: FED STD 595
....NO TEST DATA AVAILABLE....

61921 INK PARKER/JCP E20 GID: APXXXX
MANF: PARKER PEN

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data						A	K	00042.91	

05769 INK PASTE BLACK 41 GID: APXXXX
....NO TEST DATA AVAILABLE....

85492 INK PELIKAN 24 DIACETONE ALCOHOL
MANF: PELIKAN
....NO TEST DATA AVAILABLE....

20489 INK PEN 60 SILVER GID: ATXXXX
MANF: FISHER SCIENTIFIC
GFE
....NO TEST DATA AVAILABLE....

65495 INK PEN 775SL SILVER MED-PT GID: APGQXX
MANF: FISHER PEN

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							V	00003.92	71H-70F-

60806 INK PEN ACCUTEC GID: APXXXX
MANF: ACCUTEC

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data						A	A	00042.57	

65085 INK PEN SL SILVER BROAD POINT GID: APGQXX
MANF: FISHER PEN

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.0E-6	79.41	36.19	.07		A	X	00000.44	

06027 INK PENTEL PEN S360 ALL TYPES GID: APXXXX
MANF: PENTEL CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data						A	V	00025.21	

06438 INK PHENOL 82L22G1 BLACK GID: APXXXX
MANF: INDEPENDENT INK
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005704 4

60778 INK PILOT FINELINER SWPP BLACK GID: APXXXX
MANF: PILOT CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	20690.00	

TOXICITY

60777 INK PILOT FINELINER SWPP BLUE GID: APXXXX
MANF: PILOT CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.85	

TOXICITY

60776 INK PILOT FINELINER SWPP GREEN GID: APXXXX
MANF: PILOT CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00021.28	

TOXICITY

60832 INK PILOT FINELINER SWPP RED GID: APXXXX
MANF: PILOT CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00018.75	

TOXICITY

62353 INK PILOT RAZOR POINT SW10PP GID: APXXXX
MANF: PILOT CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00009.99	

TOXICITY

20348 INK PM39 BLACK GID: APXXXX
MANF: BIC INC SPEC: ST20P623-01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.03	.00		168H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00058.78	168H-70F-

TOXICITY

64244 INK POLY PRINT 45NL75/45NL99 GID: APXXXX
MANF: COLONIAL PRINTING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.012	0.003		04.10	NONE
B	1	024.5	014.5	0.013	0.003	00.20	07.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.3E-6	.64	.20	.28	168H-70F-
					.02H-250F-

ODOR

RT	RT	WEIGHT	CURE
	A	00015.19	

TOXICITY

61152 INK PRINTERS A-M CS 174C BLACK GID: APXXXX
....NO TEST DATA AVAILABLE....

80269 INK PRINTERS BLACK D6668 ON #60 SCOTT PAPER GID: APXXXX
MANF: GFE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
X	A	21.020	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005705 6

20531 INK RETARDER PAT715/T950 GID: APXXXX

MANF: ADVANCED INK INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00020.19	

TOXICITY

20277 INK S1141 BLACK GID: APXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	9.51	.02	9.05	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06370 INK S66-13 ROCKET RED GID: APXXXX

MANF: DAYGLO COLOR CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.001	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.001	0.003		07.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.5E-6	9.42	.52	.16	48H-70F- 24H-70F-

ODOR

RT	RT WEIGHT	CURE
X	X 00008.82	24H-70F- 48H-70F- 24H-150F-

TOXICITY

06371 INK S66-16 ARC YELLOW GID: APXXXX

MANF: DAYGLO COLOR CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.001	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.001	0.003	01.70	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.5E-6	10.54	.73	.20	

ODOR

RT	RT WEIGHT	CURE
A	B 00005.61	24H-70F- 24H-150F-

TOXICITY

06369 INK S66-17 SATURN YELLOW GID: APXXXX

MANF: DAYGLO COLOR CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.001	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.001	0.003	01.19	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.5E-6	10.28	.51	.17	48H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
	X 00008.01	48H-70F- 24H-150F-

TOXICITY

06372 INK S66-18 SIGNAL GREEN GID: APXXXX

MANF: DAYGLO COLOR CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.001	0.003	00.00	00.00	NONE
B	1	025.9	014.3	0.001	0.003		06.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.5E-6	12.77	.85	.21	

ODOR

RT	RT WEIGHT	CURE
A	B 00005.79	24H-70F- 24H-150F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005706 8

62540 INK SCREEN DAYGLO SUPER 67 GID: DZCCXX
MANF: STEVEN LABEL CORP SPEC: MIL-P-38477

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.004	0.003	00.00	00.00	NONE
B	1	025.9	014.3	0.004	0.003		06.80	NONE
B	1	030.0	009.0	0.004	0.003		08.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.52	

TOXICITY

61014 INK SERIES 3900 HT9040 GID: APCUXX
MANF: COLONIAL PRINTING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	4.00	.07	2.95	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05853 INK SERIES 39000 GID: APXXXX
....NO TEST DATA AVAILABLE....

20743 INK SERIES 4500 45NL75/82853 GID: APXXXX
MANF: COLONIAL PRINTING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.005	0.010		10.60	NONE
C	1	025.9	014.3	0.005	0.010	01.17	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	8.0E-6	.57	.05		.05H-250F- 168H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00024.64	.05H-250F- 168H-70F-

TOXICITY

06486 INK SHARPIE 3000 GID: APXXXX
MANF: SANFORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	B	00000.24	24H-70F- 24H-150F-

TOXICITY

20350 INK SHARPIE PEN 59 GID: ATXXXX
MANF: SANFORD CORP SPEC: ST20 P674-01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.02	.00		168H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00058.42	168H-70F-

TOXICITY

20537 INK SILICONE BASE GID: APXXXX
....NO TEST DATA AVAILABLE....

63482 INK SILKSCREEN RED GID: APXXXX
MANF: PLASTISOL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.4E-6	31.39	14.35	.06	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60734 INK STENCIL BLACK GID: APXXXX
MANF: MARSH STENCIL SPEC: TT-I-1795T3

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.2E-6	4.25	.05		24H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005707 T

60734 INK STENCIL BLACK (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					24H-150F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE

06500 INK SUPER 67 ARC YELLOW GID: APXXXX
MANF: STEVEN LABEL CORP
....NO TEST DATA AVAILABLE....

06501 INK SUPER 67 ROCKET RED GID: APXXXX
....NO TEST DATA AVAILABLE....

06499 INK SUPER 67 SATURN YELLOW GID: APXXXX
MANF: STEVEN LABEL CORP
....NO TEST DATA AVAILABLE....

06498 INK SUPER 67 SIGNAL GREEN GID: DZCCXX
MANF: STEVEN LABEL CORP SPEC: MIL-P-38477

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.004	0.003		05.90	NONE
B	1	030.0	009.0	0.004	0.003		06.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.72	

64180 INK TEC BLACK GID: APXXXX
MANF: SANFORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.005			02.00	NONE
A	1	025.9	014.3	0.005			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00000.18	

63483 INK TEC BLACK #1501
MANF: SANFORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.2E-6	21.58	13.48	1.16	504H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

63995 INK TMS ON KYNAR/VITON SHEETS GID: APCJDE
MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.020		00.05	01.20	NONE
A	1	030.0	010.0	0.020		00.05	01.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20048 INK TROJAN OPAQUE BLACK GID: APXXXX
MANF: SUPERIOR MRKNG EQUIP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.7E-7	10.29	.00		24H-70F-
					24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00001.63	113H-70F-
		24H-150F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005708 1

20047 INK TROJAN OPAQUE SILVER GID: APXXXX
MANF: SUPERIOR MRKNG EQUIP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.3E-7	35.24	.12		24H-70F- 24H-150F-

ODOR / TOXICITY

ODOR RT	TOXICITY RT	WEIGHT	CURE
A	X	00001.92	26H-70F- 24H-150F-

80153 INK TY609 MARKING BLACK
MANF: INDEPENDENT INK
....NO TEST DATA AVAILABLE....

20334 INK TYPEWRITER RIBBON GID: APXXXX
MANF: IBM CORP SPEC: ST18R131

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.44	3.64	.00	

ODOR / TOXICITY

ODOR RT	TOXICITY RT	WEIGHT	CURE
	X	56.665	168H-70F-

05258 INK UNIGLAZE C1204 EPOXY GID: APBGXX
MANF: UNION INK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		03.70	NONE
A	1	030.0	010.0	0.002	0.003		03.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1500	72	70	0.001	0	20
B	PNEU	1500		70	0.003	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.7E-7	7.53	.01		168H-70F- 24H-150F-

ODOR / TOXICITY

ODOR RT	TOXICITY RT	WEIGHT	CURE
A	X	00009.79	168H-70F- 24H-150F-

05239 INK UNIGLAZE C1336 EPOXY BLACK GID: APBMXX
MANF: UNION INK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.002	0.003		02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.5E-6	10.29	.54		168H-70F- 24H-150F-

ODOR / TOXICITY

ODOR RT	TOXICITY RT	WEIGHT	CURE
A	X	00008.71	168H-70F- 24H-150F-

63668 INK UNIGLAZE UGLZ8000 BLACK GID: APBMXX
MANF: UNION INK SPEC: REDUC UGLZ-1498

THERMAL VACUUM STABILITY

RT PRESS TML% VCM% RML% CURE
No test data

ODOR / TOXICITY

ODOR RT	TOXICITY RT	WEIGHT	CURE
	X	00002.21	240H-70F-

62430 INK UNIMARK 960/JPC K10 PAPER GID: APXXXX
MANF: UNI-MARK

THERMAL VACUUM STABILITY

RT PRESS TML% VCM% RML% CURE
No test data

ODOR / TOXICITY

ODOR RT	TOXICITY RT	WEIGHT	CURE
	X	00012.32	

06306 INK WARNOWINK M-9-N WITH DEPTHANE GLOSS NO. 1 OVERCOAT
MANF: DEFT
HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.010	0.003	00.00	00.00	NONE
B	1	023.8	014.5	0.010	0.003		07.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

No test data

MSFC-HDBK-527 REV F 9999942 0005709 3

Information Handling Services, 2000

06306 INK WARNOWINK M-9-N WITH DEPTHANE GLOSS NO. 1 OVERCOAT (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.4E-6	4.60	.53		24H-70F- 24H-150F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00034.30	24H-70F- 24H-150F-

TOXICITY

05231 INK WORNOW 50-100R/9 WHITE GID: APGUXX

MANF: HYSOL/DEXTER SPEC: MB0190-003T2

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	B	00008.41	168H-70F- 24H-150F-

TOXICITY

20889 INK WORNOW SERIES M GR/RED/BLU GID: APXXXX

MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.63	.05	.00	2H-151F- 72H-124F-0psiaVACUUM

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

63520 INK WORNOWINK M-6-N/CAT A GID: APXXXX

MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003	0.003	00.70	04.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.4E-6	6.26	.06	.31	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05726 INK WORNOWINK M-9-N/100 PARTS BY WEIGHT OF INK BLENDED WITH 4.9 PARTS BY WEIGHT OF CATALYST GID: APBGXX

MANF: HYSOL/DEXTER SPEC: T0607 & V0422

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.013	0.003	00.00	00.00	NONE
B	1	023.8	014.5	0.013	0.003		08.80	NONE
C	2	025.9	014.3	0.001	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.001	0.003	01.71	12.00	T NONE
A	1	030.0	010.0	0.002			04.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.76	.22	.00	

ODOR

RT	RT	WEIGHT	CURE
X	X	00039.16	24H-70F- 24H-150F-

TOXICITY

00030 INK WORNOWINK M-O-N/CAT A GID: APBGXX

MANF: HYSOL/DEXTER SPEC: MB0190-006

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.30	NONE
B	2	025.9	014.3	0.010	0.003		00.20	NONE
B	1	025.9	014.3	0.010	0.003	00.54	09.00	SMALL
A	1	030.0	010.0	0.002		00.31	02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.68	.00	.00	2H-150F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00012.49	24H-70F- 168H-70F- 24H-150F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005710 T

60346 INSULATION 60
MANF: 3M CO
....NO TEST DATA AVAILABLE....

05183 INSULATION ABLATIVE EPOXY/POLYIMIDE 183K2 GID: EPBGXX
MANF: SPEC: MB0130-033
....NO TEST DATA AVAILABLE....

61583 INSULATION AFRSI WITH DISILAZANE Z6079 GID: FJHOXX
MANF: DOW CORNING SPEC: MB0115-021 MB0135-085
JOHNS-MANVILLE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.500			00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.1E-6	.81	.04	.65	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61584 INSULATION AFRSI WITH SILANE Z6070 GID: FJHOXX
MANF: HI TEMP INSULATION SPEC: MB0135-085

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.500		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.2E-6	.19	.00	.07	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63134 INSULATION AL FOIL ON BETA CLOTH GID: CKXXXX
MANF: MCDONNELL DOUGLAS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.125			02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20072 INSULATION ARMAFLEX (FR) NEOPRENE GID: CADBXX
MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.500			00.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62263 INSULATION ARMAFLEX RUBBER GID: FMHDXX
MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	100.0	014.7	0.045		05.00	10.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.57	2.41	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62264 INSULATION ARMAFLEX/ARMSTRONG 520 GID: FMHDBG
MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	100.0	014.7	0.500		05.05	09.60	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	13.58	3.15		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

MSFC-HDBK-527 REV F 9999942 0005711 1

Information Handling Services, 2000

80209 INSULATION BLACK FROM STRANDED ELECTRICAL WIRE GID: CKXXXX
MANF: BARCEL WIRE AND CABLE SPEC: MIL-W-81381/17-22-0

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	1.23	.01	.55	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

63394 INSULATION BLANKET AU/AL COATED
MANF: MARTIN MARIETTA SPEC: STM A567, STM A569, STM A568, STM-Y-985

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.060		00.138	06.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63395 INSULATION BLANKET AU/AU COATED POLYIMIDE
MANF: MARTIN MARIETTA SPEC: STM A567, STM-Y-985, STM A568

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.060			03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63524 INSULATION BLANKET DP50392 TYPE 2 MYLAR/KAPTON GID: FJCDXX
MANF: HUGHES AIRCRAFT SPEC: HMS 20-2006

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.002		00.55	11.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85498 INSULATION BLANKET DP50392 TYPE 3 MYLAR/KAPTON/GLASS
MANF: HUGHES AIRCRAFT
....NO TEST DATA AVAILABLE....

85389 INSULATION BLANKET DP50392 TYPE 8 KAPTON/GLASS
MANF: HUGHES AIRCRAFT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61649 INSULATION BLANKET FLUORGLAS 385-3
MANF: DODGE
FLUORGLAS
SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
S								NONE
S								NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.10	.01		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

62288 INSULATION BLANKET KAPTON/AL/MYLAR/DACRON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.052			02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62357 INSULATION BLANKET KAPTON/DACRON/NOMEX GID: FJCDCB
MANF: MCDONNELL DOUGLAS SPEC: MB0135-038T2, MB0135-048T2, MB0135-042, MIL-T-43636T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.040			01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005712 3

62301 INSULATION BLANKET KAPTON/MYLAR/DACRON GID: FJCDCC

MANF: GENERAL ELECTRIC

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.016			02.70	NONE	No test data		No test data							

06057 INSULATION BLANKET MC364-0011 GID: CKXXXX

MANF: HI TEMP INSULATION

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.400			03.00	NONE	No test data		No test data							

63128 INSULATION BLANKET MIN-K FAB/STEEL GID: FCXXXX

MANF: TRW

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.400			01.50	NONE	No test data		No test data							

06464 INSULATION BLANKET SILICONE/S-GLASS/Q-FELT GID: FJXXXX

MANF: JOHNS-MANVILLE SPEC: MB0135-085

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.500		00.00	00.00	NONE	No test data		No test data							
A	1	025.9	014.3	0.500		00.00	00.00	NONE										
A	1	030.0	009.0	0.500		00.00	00.00	NONE										

60285 INSULATION BLASTAPE II G120 MX4702 GID: FJXXXX

MANF: JOHNS-MANVILLE

....NO TEST DATA AVAILABLE....

63130 INSULATION CELLULOSE WITH FIREPROOFING GID: CKAUXX

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7			00.00	00.00	NONE	No test data		No test data							

60386 INSULATION CEMA FIBER 111 GID: CKXXXX

MANF: JOHNS-MANVILLE SPEC: USBI99608-0103

....NO TEST DATA AVAILABLE....

06474 INSULATION CERACHROME CERAMIC INORGANIC

MANF: JOHNS-MANVILLE

....NO TEST DATA AVAILABLE....

61288 INSULATION CHOTRAP CM26-3 GID: FJXXXX

MANF: CHOMERICS

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	025.9	014.3	0.033			10.40	T NONE	No test data		No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.3E-6	.09	.01	.02	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
	K 00020.46	

61151 INSULATION CORK GID: FJFRXX

MANF: ARMSTRONG SPEC: HH-C-576

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	14.45	.56		

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005713 5

63131 INSULATION CORK AB600 GID: CKFRXX
MANF: SOUTHLAND CORK
SPEC: STW4-2700

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.250		00.17	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

69806 INSULATION CORK COMPOSITE P50
MANF: SHELLER GLOBE
....NO TEST DATA AVAILABLE....

20106 INSULATION ELECTRICAL FORMVAR GID: CKXXXX
....NO TEST DATA AVAILABLE....

20159 INSULATION ELECTRICAL RAG PAPER GID: FJGMXX
MANF: C D LA MOREE CO
SPEC: MIL-I-695TR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.007		00.04	12.00	T NONE
X	1	023.8	014.5	0.007		01.02	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT
A	V	00013.08

TOXICITY

CURE

64051 INSULATION ENAMEL #300 RED GID: AKXXXX
MANF: SCHENECTADY CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.5E-6	1.04	.20	.36	4H-200F- .5H-300F- .5H-375F-

ODOR

RT	RT	WEIGHT
No test data		

TOXICITY

CURE

61698 INSULATION FELT NOMEX TYPE E GID: BIBVXX
MANF: GLOBE ALBANY CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.8E-7	1.11	.00		

ODOR

RT	RT	WEIGHT
A	K	00020.31

TOXICITY

CURE

06473 INSULATION FIBERFRAX 970A CERAMIC GID: DOHOHO
MANF: CARBORUNDUM
....NO TEST DATA AVAILABLE....

63132 INSULATION FIBERGLASS BUILDING PINK GID: CKFVXX
MANF: OWENS CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	2.500		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60711 INSULATION FIBERMAT 2539 GID: DIXXXX
MANF: 3M CO
SPEC: HMS 13-1696

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.005			02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.19	.02	.00	

ODOR

RT	RT	WEIGHT
No test data		

TOXICITY

CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005714 7

05021 INSULATION FLEX ALUMINA SILICATE GID: CKHKXX
MANF: JOHNS-MANVILLE SPEC: MB0135-031 MB0135-031T8 MB0135-031T24

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.250		00.00	00.00	NONE

FSC: RT FLUID NAME — No test data

OXYGEN COMP: RT TEST PRESS IMPACT TEMP THICK #REACT #TEST — No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.3E-6	.17	.00		

ODOR: RT — No test data

TOXICITY

RT	RT WEIGHT	CURE
X	00009.62	

06117 INSULATION FLEX MIN-K TY5 HT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.21	.00	.00	

ODOR: RT — No test data

TOXICITY: No test data

61699 INSULATION FOAM 402 POLYURETHANE GID: ETCQXX
MANF: COOK PAINT & VARNISH SPEC: MB0130-079

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.460		00.20	09.00	NONE
X	1	023.8	014.5	0.460		00.90	12.00	T NONE

FSC: RT FLUID NAME — No test data

OXYGEN COMP: RT TEST PRESS IMPACT TEMP THICK #REACT #TEST — No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.0E-6	9.39	.00		24H-150F-

ODOR: RT — A

TOXICITY

RT	RT WEIGHT	CURE
X	00003.19	24H-150F-

62940 INSULATION FOAM ABLESTICK/ECCOSPHERES S1 GID: CAXXXX
MANF: MOTOROLA SPEC: PD-6400520

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.480			01.50	NONE

FSC: RT FLUID NAME — No test data

OXYGEN COMP: RT TEST PRESS IMPACT TEMP THICK #REACT #TEST — No test data

62946 INSULATION FOAM ALBI-COTE FRL 5A GID: CAXXXX
MANF: STANCHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.250			01.70	NONE

FSC: RT FLUID NAME — No test data

OXYGEN COMP: RT TEST PRESS IMPACT TEMP THICK #REACT #TEST — No test data

62941 INSULATION FOAM ALBICOTE GID: CAXXXX
MANF: STANCHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7				02.30	NONE

FSC: RT FLUID NAME — No test data

OXYGEN COMP: RT TEST PRESS IMPACT TEMP THICK #REACT #TEST — No test data

62942 INSULATION FOAM ALBICOTE FRL 3A GID: CAXXXX
MANF: STANCHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.250			01.30	NONE

FSC: RT FLUID NAME — No test data

OXYGEN COMP: RT TEST PRESS IMPACT TEMP THICK #REACT #TEST — No test data

63133 INSULATION FOAM ARMAFLEX GID: CBXXXX
MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.750			01.00	NONE

FSC: RT FLUID NAME — No test data

OXYGEN COMP: RT TEST PRESS IMPACT TEMP THICK #REACT #TEST — No test data

20710 INSULATION FOAM ARMAFLEX 22 NEOPRENE GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.3	1.000		00.12	12.00	T NONE

FSC: RT FLUID NAME — No test data

OXYGEN COMP: RT TEST PRESS IMPACT TEMP THICK #REACT #TEST — No test data

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005715 9

20710 INSULATION FOAM ARMAFLEX 22 NEOPRENE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	1.000		00.29	10.00	T MOD
X	1	025.9	014.3	1.000		00.08	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

05110 INSULATION FOAM BX249N POLYURETHANE GID: CACQXX

MANF: STEPAN CHEMICAL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.750		00.31	12.00	T NONE
I	1	030.0	008.0	1.000		01.43	12.00	T NONE
I	1	040.0	008.0	1.000		02.29	12.00	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.0E-7	8.34	.00		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62947 INSULATION FOAM BX250 GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	015.0	014.7	1.000			02.00	NONE
A	1	020.9	014.7	0.310			02.00	NONE
B	1	020.9	014.7	1.000			08.00	NONE
A	1	020.9	014.7	1.375	0.002		02.00	SMALL
A	1	025.0	014.7	1.000			02.00	NONE
I	1	030.0	014.7	1.000		00.60	15.00	T NONE
I	1	050.0	014.7	1.000		00.88	15.00	T NONE
A	1	100.0	014.7	1.000		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62950 INSULATION FOAM BX250 COATED WITH D65 GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.375			01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62951 INSULATION FOAM BX250 FRL COATED GID: CAXXXX

MANF: FABRIC RESEARCH LAB
MARTIN MARIETTA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	015.0				04.83	NONE
A	1	020.9	014.7	0.500			01.50	NONE
B	1	025.9	014.5			00.26	09.00	NONE
I	1	030.0	014.5			00.34	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05111 INSULATION FOAM BX250 VARIOUS RATIO POLYURETHANE GID: ETCQXX

MANF: STEPAN CHEMICAL CO SPEC: MB0130-077

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	1.000	0.003	00.22	06.50	NONE
I	2	023.8	014.5	0.500			07.60	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.8E-7	11.01	.17		24H-150F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
A	X 00002.78	24H-150F-

TOXICITY

62952 INSULATION FOAM BX250 WITH TIO2 FILLER GID: CIFXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000	0.100		05.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0005716 0

Information Handling Services, 2000

62949 INSULATION FOAM BX250/COATING RL3788 GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.375			01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62948 INSULATION FOAM BX250/COATING V555 VINYL GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7			00.00	00.00	NONE
A	1	020.9	014.7				01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62953 INSULATION FOAM BX250/FRL COATED/DMSO GEL GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	1.000			03.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85374 INSULATION FOAM BX250/HYPALON COATED

MANF: STEPAN CHEMICAL/GACO WESTERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.5	1.000	0.125	00.13	06.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85474 INSULATION FOAM BX442R(X1057-137A) POLYURETHANE

MANF: STEPAN CHEMICAL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	024.5	014.5	01.00	0.062	00.02	09.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85438 INSULATION FOAM BX443R POLYURETHANE GID: CKXXXX

MANF: STEPAN CHEMICAL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	024.5	014.5	1.000	0.062	00.10	6.25	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61540 INSULATION FOAM CEI 10 FLUOROCARBON GID: CKCQEF

MANF: HAMILTON STANDARD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.566	0.030		01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00020.07	

80237 INSULATION FOAM CELLULAIRE H920A PVC GID: CAXXXX

MANF: L'AIR LIQUIDE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.200			02.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.92	.00	.31	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

61675 INSULATION FOAM CHEMLON 100TA NRL2-2 GID: CCXXXX

MANF: CHEMTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			00.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0005717 2

Information Handling Services, 2000

61675 INSULATION FOAM CHEMLON 100TA NRL2-2 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	.87	.21	.23	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

61010 INSULATION FOAM CHEMLON 100TA PC GID: CACDXX

MANF: CHEMTRONICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.2E-6	.67	.03	.37	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

60622 INSULATION FOAM CHEMLON 103 GID: CAXXXX

MANF: CHEMTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	024.5	014.5	1.000			01.80		NONE
A	1	025.9	014.3	1.000			01.30		NONE
C	2	025.9	014.3	0.118			00.30		NONE
C	1	025.9	014.3	0.118		01.80	11.90	T	NONE
A	1	025.9	014.3	0.250			00.90		NONE
B	1	025.9	014.3	0.130			09.90		SMALL
A	1	030.0	010.4	0.800			01.60		NONE
A	1	030.0	010.0	0.260			00.90		SMALL
X	1	100.0	020.2	0.900		24.00	12.00	T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.46	.02		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	K 00014.87	

61009 INSULATION FOAM CHEMLON 200 FF NRL25 GID: ESXXXX

MANF: CHEMTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.800			00.60	NONE
A	1	030.0	010.4	0.800			00.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.2E-6	.66	.00	.50	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	K 00019.85	

60695 INSULATION FOAM CHEMLON 203 GID: CAXXXX

MANF: CHEMTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
C	2	025.9	014.3	0.170			00.90		NONE
C	1	025.9	014.3	0.170		00.90	12.00	T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60623 INSULATION FOAM CHEMLON 403 GID: CAXXXX

MANF: CHEMTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	025.9	014.3	0.900		00.00	00.00		NONE
A	1	030.0	010.4	0.900		00.00	00.00		NONE
X	1	100.0	020.2	0.900		05.50	10.40	T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.0E-6	1.44	.21	1.05	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	K 00020.48	

MSFC-HDBK-527 REV F 9999942 0005718 4

Information Handling Services, 2000

61107 INSULATION FOAM CHEMLON 500FC POLYIMIDE GID: CACDXX

MANF: CHEMTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	2.500			01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.8E-6	1.09	.00	.79	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60634 INSULATION FOAM CHEMLON 503 GID: CAXXXX

MANF: CHEMTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	1.000			00.10	NONE
X	2	025.9	014.3	0.160		00.30	12.00 T	NONE
X	1	025.9	014.3	0.160		01.20	12.00 T	NONE
A	1	030.0	010.4	1.000			00.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00010.17	

TOXICITY

62429 INSULATION FOAM CHEMLON 504 POLYIMIDE GID: CACDXX

MANF: CHEMTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.933			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.49	.05		4H-250F-0psia10E-3 TORR

ODOR

RT	RT WEIGHT	CURE
A	K 00011.52	

TOXICITY

69811 INSULATION FOAM CHEMLON POLYIMIDE

MANF: CHEMTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	50	20	70	0.250	00	20

62956 INSULATION FOAM CHEMPOL/SOLITHANE 113/300 GID: CACQXX

MANF: MARTIN MARIETTA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	2.800	0.050	00.12	04.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60630 INSULATION FOAM CONFOR C40 GID: CAXXXX

MANF: SPECIALTY COMPOSITES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	020.2	0.500		10.00	12.00 T	MOD
X	1	100.0	020.2	0.500		10.00	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.1E-6	1.24	.15	.40	

ODOR

RT	RT WEIGHT	CURE
A	A 00019.99	

TOXICITY

60632 INSULATION FOAM CONFOR C45 GID: CAXXXX

MANF: SPECIALTY COMPOSITES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	020.2	0.500		21.30	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005719 6

60632 INSULATION FOAM CONFOR C45 (cont)

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	100.0	020.2	0.500		11.30	12:00	T MOD										

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	4.9E-6	16.41	9.16	.59		A	K 00020.38	

60631 INSULATION FOAM CONFOR C47 GID: CAXXXX
MANF: SPECIALTY COMPOSITES

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	100.0	020.2	0.500		20.00	12.00	T MOD		No test data		No test data						
X	1	100.0	020.2	0.500		12.00	12.00	T MOD										

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.25	.13	.52		A	K 00019.89	

62958 INSULATION FOAM COOK GREEN 977-G-325 SPRAY-ON GID: CAXXXX

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	020.9	014.7	1.470		00.06	12.00	T NONE		No test data		No test data						
A	1	020.9	014.7	1.900	0.100		04.50	NONE										

62957 INSULATION FOAM COOK YELLOW/GREEN GID: CAXXXX

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.900			01.50	NONE		No test data		No test data						

65311 INSULATION FOAM CPR1002 POLYURETHANE GID: CACQXX

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	015.0				05.00	NONE		No test data		No test data						

69861 INSULATION FOAM CPR1061 COATED WITH ALBI-COTE FRL WITH COATED SEMICIRCLE GID: CAXXXX
MANF: STANCHEM SPEC: STW4-3259:COATING STW5-3180:FOAM
UPJOHN

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.250			04.25	NONE		No test data		No test data						

62983 INSULATION FOAM CPR1061 FR GID: CAXXXX

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7	0.500			06.30	NONE		No test data		No test data						

65544 INSULATION FOAM CPR1061 WITH ALBI COTE COATING GID: EXXXXX
MANF: M T I CHEMICAL SPEC: STW4-3259:CTNG STW5-3180:FOAM
STANCHEM

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.250			01.50	NONE		No test data		No test data						

69947 INSULATION FOAM CPR1061 WITH ALBICOTE FRL
MANF: MORTON THIOKOL

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7				02.50	NONE		No test data		No test data						

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005720 2

62356 INSULATION FOAM CPR306-2/REFSET COATED GID: CAHSXX

MANF: CPR DIVISION
RAYBESTOS-MANHATTAN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	1.84	.04	.27	.5H-160F-SECOND COAT APPLIED THEN CURED .67H-75F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65221 INSULATION FOAM CPR330-32 POLYISOCYANURATE GID: CAXXXX

MANF: UPJOHN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			04.42	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63122 INSULATION FOAM CPR402 POUR GID: CAXXXX

MANF: UPJOHN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			00.35	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62960 INSULATION FOAM CPR488 GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			04.50	NONE
A	1	020.9	015.0				04.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62961 INSULATION FOAM CPR488 CONDENSATE GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			03.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62973 INSULATION FOAM CPR488 WET SPRAY GID: CAXXXX

MANF: MMC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.625	0.100		06.00	NONE
A	1	020.9	014.7	2.700			05.20	NONE
A	1	020.9	014.7	2.100			03.00	NONE
I	1	030.0	014.7	2.500		02.00	12.00 T	NONE
A	1	030.0	014.7	2.100			05.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62975 INSULATION FOAM CPR488/22592 BLACK CARBON FILLED CONDUCTIVE GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	1.000	0.100		08.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65059 INSULATION FOAM CPR488/BX250 WITH CONATHANE GID: CACQXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			02.75	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65060 INSULATION FOAM CPR488/BX250 WITH EPOXY PRIMER GID: CACQXV

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			05.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005721 4

62963 INSULATION FOAM CPR488/ECCOBOND 59K ADHES GID: CAXXXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000	0.100	00.20	00.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62964 INSULATION FOAM CPR488/ECCOBOND 60L ADHES GID: CAXXXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000	0.100	00.92	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.77	.11	.00	16H-70F-48H-122F-0psiaVACUUM

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62965 INSULATION FOAM CPR488/ED199 COATED GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000	0.100		02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62966 INSULATION FOAM CPR488/FRL COATED/DMSO GEL GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	1.000	0.100		03.50	MOD
A	1	020.9	014.7	1.250	0.100		02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62967 INSULATION FOAM CPR488/FRL COATED/E GLYCOL GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.250	0.100		00.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62971 INSULATION FOAM CPR488/FRL3 3193 TY2 COATED GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.500	0.100		02.50	NONE
B	1	025.9	014.5	1.500	0.100		07.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62972 INSULATION FOAM CPR488/FRL3 AND PERSERVO COATED GID: CAXXXX

MANF: PERSERVO PAINT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	1.400	0.100		07.00	NONE
B	1	025.9	014.5	1.400	0.100		10.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62968 INSULATION FOAM CPR488/FRL3 COATED GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.500	0.100		01.80	NONE
A	1	020.9	014.7	1.000	0.125	00.13	04.50	NONE
A	1	025.9	014.7	1.500	0.100		04.50	NONE
A	1	025.9	014.3	1.000	0.125	00.20	05.75	NONE
B	1	30.0	9.00	1.00	0.125	00.22	7.25	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62969 INSULATION FOAM CPR488/FRL3 COATED/EMULSION GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.125	0.100		03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005722 6

62969 INSULATION FOAM CPR488/FRL3 COATED/EMULSION (cont)

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.500		00.00	00.00	NONE									

62970 INSULATION FOAM CPR488/FRL3 TY2 COATED GID: CAXXXX

MANF: MARTIN MARIETTA

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.5	1.000	0.100		05.00	NONE	No test data	No test data							
B	1	030.0	014.5	1.000	0.100		07.50	NONE									
I	1	035.0	014.5	1.000	0.100	01.00	12.00	T NONE									

65064 INSULATION FOAM CPR488/ISOCYANURATE GID: CAXXXX

MANF: UPJOHN

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	015.0	0.500			03.50	NONE	No test data	No test data							

62974 INSULATION FOAM CPR488/TANCO 9708 COATED GID: CAXXXX

MANF: MARTIN MARIETTA

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.5	1.000	0.100		03.00	NONE	No test data	No test data							
A	1	030.0	014.5	1.000	0.100		02.50	NONE									
B	1	035.0	014.5	1.000	0.100		10.50	SMALL									

62976 INSULATION FOAM CPR50 GID: CAXXXX

MANF: MARTIN MARIETTA

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	2.600	0.100		06.00	NONE	No test data	No test data							

62977 INSULATION FOAM CPR50A GID: CAXXXX

MANF: MARTIN MARIETTA

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.800	0.100		05.50	NONE	No test data	No test data							

63047 INSULATION FOAM CPR920-9-2 POLYURETHANE PS GID: CACQXX

MANF: UPJOHN

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	020.9	014.7	2.500			00.50	NONE	No test data	No test data							
C	1	020.9	014.7	2.500		00.05	06.00	T SMALL									

62959 INSULATION FOAM CPR920-9-2/HFR2200 PS GID: CACQXX

MANF: GACO WESTERN INC
UPJOHN

SPEC: STW5-3180

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.250			05.80	NONE	No test data	No test data							

60840 INSULATION FOAM CPR9545 POLYISOCYANURATE GID: ETCQXX

MANF: UPJOHN

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	1.000			01.30	SMALL	No test data	No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005723 8

60840 INSULATION FOAM CPR9545 POLYISOCYANURATE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
X	00003.05	

TOXICITY

61097 INSULATION FOAM CPR9700 GID: CAXXXX

MANF: UPJOHN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.1E-6	5.03	1.57	.32	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62115 INSULATION FOAM CPR9700-1.45S POLYURETHANE GID: CACQIE

MANF: UPJOHN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.200		00.54	12.00	T MOD
X	1	025.9	014.3	0.200		01.74	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00019.66	

TOXICITY

62159 INSULATION FOAM CPR9700-1.75 POLYURETHANE GID: CACQXX

MANF: DAVIS INTERNATIONAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.900		00.83	09.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00020.18	

TOXICITY

62114 INSULATION FOAM CPR9700-1.75XF POLYURETHANE GID: CACQXX

MANF: UPJOHN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	1.000		00.25	12.00	T MOD
X	1	025.9	014.3	1.000		01.38	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.93	1.88		

ODOR

RT	RT WEIGHT	CURE
A	X 00006.46	

TOXICITY

62116 INSULATION FOAM CPR9700-20 POLYURETHANE GID: CACQIE

MANF: UPJOHN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.200		00.39	11.80	T MOD
X	1	025.9	014.3	0.200		01.32	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00020.11	

TOXICITY

62978 INSULATION FOAM CPRTC263-93 GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	1.400	0.100		08.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.54	.06	.00	48H-151F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005724 T

62978 INSULATION FOAM CPRTC263-93 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					24H-212F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE

62979 INSULATION FOAM CREST 2460 GID: CAXXXX

MANF: CREST PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	0.153		00.22	12.00	T NONE
X	1	025.9	014.3	0.122		00.26	12.00	T MOD
I	1	025.9	014.3	0.108		00.20	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60639 INSULATION FOAM CREST 3030 TAN GID: CAXXXX

MANF: CREST PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	1.000		00.70	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00020.63	

60640 INSULATION FOAM CREST 7530 TAN GID: CAXXXX

MANF: CREST PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	1.000		00.80	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00020.51	

62293 INSULATION FOAM DENSITE 2 GID: CAXXXX

MANF: TENNECO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	5.000			00.30	NONE
I	1	025.9	014.3	5.000		00.17	05.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	13.46	7.02	.27	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

06458 INSULATION FOAM DENSITE 2 POLYESTER URETHANE 5 GID: CACBCQ

MANF: TENNECO

....NO TEST DATA AVAILABLE....

62292 INSULATION FOAM DENSITE 3 GID: CAXXXX

MANF: TENNECO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	5.000			03.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65459 INSULATION FOAM DENSITE 4 GUARDIAN/G 8003 GID: CAXXXX

MANF: GENERAL FOAM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	1.000			01.10	NONE
C	1	030.0	010.0	1.000		00.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005725 1

65459 INSULATION FOAM DENSITE 4 GUARDIAN/G 8003 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	11.47	5.37	.19	

ODOR

RT	RT WEIGHT	CURE
A	K 00021.84	

TOXICITY

06459 INSULATION FOAM DENSITE EN-3 POLYETHER GID: CAXXXX

MANF: TENNECO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	1.000			04.00	NONE
A	1	030.0	009.0	1.000			03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.2E-6	11.16	4.39	.37	

ODOR

RT	RT WEIGHT	CURE
	K 00020.38	

TOXICITY

80235 INSULATION FOAM DIVINYCELL HT-50 GID: CAXXXX

MANF: DIAB-BARRACUDA

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	3.31		.55	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62980 INSULATION FOAM ECCOFOAM 12-2H GID: CACQXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.500			00.20	NONE
X	2	030.0	010.0	1.500		00.50	11.80	NONE
X	1	030.0	010.0	1.500		02.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.25	.02	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62981 INSULATION FOAM ECCOFOAM 12-6H GID: CACQXX

MANF: ESA/ERNO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.500			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06643 INSULATION FOAM ECCOFOAM FPH 12-6H POLYURETHANE GID: CAXXXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.270			01.90	NONE
X	1	020.9	014.7	0.270		00.50	11.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.25	.15	.00	24H-77F- 3H-300F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05554 INSULATION FOAM ECCOFOAM FPH POLYURETHANE GID: CACQXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	015.0	014.3	1.500			10.00	MOD
X	1	017.0	014.3	1.500		00.82	12.00	T MOD
X	1	019.0	014.3	1.500		08.70	12.00	T NONE
X	2	023.8	014.5	1.500		00.26	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0005726 3

Information Handling Services, 2000

05554 INSULATION FOAM ECCOFOAM FPH POLYURETHANE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	1.500		03.13	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.27	.01	.53	4H-158F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00020.45	

05898 INSULATION FOAM ECCOFOAM FPH/FC721 COATED GID: CECQXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.141		00.29	11.80	T MOD
I	1	030.0	010.0	0.140		00.90	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.9E-6	.51	.01	.37	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

60239 INSULATION FOAM ECCOFOAM TYPE SH GID: CACQXX

MANF: EMERSON AND CUMING SPEC: MSFC 418

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.125		01.38	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.04	.00	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00019.72	

20574 INSULATION FOAM ENSOLITE TYPE AH GID: CAXXXX

MANF: UNIROYAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.600			00.30	NONE
B	1	025.9	014.3	0.600			06.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.9E-6	10.39	5.84		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00019.75	

61293 INSULATION FOAM ENSOLITE TYPE ALF POLYURETHANE GID: CACQXX

MANF: UNIROYAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.242		00.35	11.40	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20013 INSULATION FOAM ENSOLITE TYPE ALG PVC GID: CAAEXX

MANF: UNIROYAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.300			00.20	NONE
C	1	020.9	014.7	0.300		00.20	12.00	T SMALL
A	1	020.9	014.7	0.295	0.020		03.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.0E-6	13.13	7.35		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00005.16	

20892 INSULATION FOAM EPOXY SYNTACTIC MODIFIED GID: ETABXX

MANF: ROCKWELL SPEC: MB0130-143

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.243		00.00	00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005727 5

20892 INSULATION FOAM EPOXY SYNTACTIC MODIFIED (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.243		00.06	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.7E-6	1.83	.04	.76	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62982 INSULATION FOAM ET-TPS GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	1.500			08.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61402 INSULATION FOAM ETHAFOAM 220/RUBBER RTV 560 GID: CACCXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.600			00.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05799 INSULATION FOAM FLUOREL G306/L3203-6 GID: CADEXX

MANF: RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.631			00.20	SMALL
A	1	030.0	009.0	0.548	0.032		00.40	NONE
A	1	030.0	009.0	0.631			00.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64821 INSULATION FOAM FLUOREL/URETHANE COATED GID: CACQDE

MANF: CUSTOM PACKING
RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	3.400			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61051 INSULATION FOAM GOLDEN WEST 9-12 GID: CAXXXX

MANF: GOLDEN WEST PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	020.2	0.322		03.20	11.90	T MOD
X	1	100.0	020.2	0.322		05.10	11.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.9E-6	4.81	2.07	.38	

ODOR

RT	RT WEIGHT	CURE
A	A 00020.47	

TOXICITY

61096 INSULATION FOAM GRADE 1331 GID: CAXXXX

MANF: REEVES BROS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.1E-6	.88	.03	.35	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61098 INSULATION FOAM GRADE 1830 GID: CAXXXX

MANF: WOODBRIDGE FOAM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.57	.23	3.29	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62989 INSULATION FOAM GREAT STUFF 1/2/3 GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	2.000		00.36	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0005728 7

Information Handling Services, 2000

62991 INSULATION FOAM GREAT STUFF 4,5,6 /FRL3 COATED GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	2.000			04.00	NONE
B	1	025.9	014.7	2.000			07.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65217 INSULATION FOAM GREAT STUFF WITH FRL-4 GID: CAXXXX

MANF: FABRIC RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	015.0				02.25	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61767 INSULATION FOAM HYPOL 4 URETHANE GID: ESCQXX

MANF: W R GRACE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.400			06.30	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	V	00007.31	24H-160F-

TOXICITY

20708 INSULATION FOAM HYPOL FHP3000 POLYURETHANE GID: CACQXX

MANF: W R GRACE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.317			05.50	MOD
X	2	030.0	009.0	0.317			00.90	NONE
X	1	030.0	009.0	0.317		00.32	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	B	00020.16	SEE TEST DOCUMENT

TOXICITY

65218 INSULATION FOAM INSTA FOAM WITH FRL-4 GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	015.0				06.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	10.10	.05	.00	16H-109F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60389 INSULATION FOAM INSTA KIT 115 GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			05.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60306 INSULATION FOAM INSTA POLYURETHANE GID: CACRXX

MANF: INSTA-FOAM PROD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.27	.04	.00	.5H-248F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

80290 INSULATION FOAM INTERFLO HIGH MOLECULAR WEIGHT POLYETHYLENE GID: CAXXXX

MANF: CHROMAX CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.310		0.01	11.50	T LARGE
X	1	025.9	014.3	0.312		00.01	10.00	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005729 9

80290 INSULATION FOAM INTERFLO HIGH MOLECULAR WEIGHT POLYETHYLENE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	009.0	0.310		0.01	11.50	T LARGE
X	1	030.0	009.0	0.250		00.01	12.00	T LARGE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	84.8	

65236 INSULATION FOAM ISOCYANURATE AW255 GID: CAXXXX

MANF: UPJOHN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	150.0	5.000			03.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65301 INSULATION FOAM ISOCYANURATE MO9-58-2 GID: CADUXX

MANF: ISOCYANURATE PROD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7				03.75	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65295 INSULATION FOAM ISOCYANURATE S16-49 GID: CADUXX

MANF: ISOCYANURATE PROD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7				03.87	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80283 INSULATION FOAM ISOCYANURATE S17-120B GID: CAXXXX

MANF: ISOCYANURATE PROD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000	0.125	0.15	05.25	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05705 INSULATION FOAM KOROPON SUPER/RTV560/HYPOLIN GID: CAXXXX

MANF: SPEC: MB0130-128T1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.79	.18	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

62255 INSULATION FOAM KUA/ARMALON/CSR300 ADHES GID: CACQXX

MANF: CONSOLIDATED KINETIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	1.000		00.12	11.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00029.57	

62256 INSULATION FOAM KUA/BLACK VINYL COVER GID: CACQXX

MANF: CONSOLIDATED KINETIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	1.000		00.59	11.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06084 INSULATION FOAM KUA100 GID: CACQXX

MANF: CONSOLIDATED KINETIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	017.0	014.3	3.633			04.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005730 5

06084 INSULATION FOAM KUA100 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	019.0	014.3	0.800			06.90	SMALL
X	1	023.8	014.5	1.000		00.16	12.00	T MOD
I	1	025.9	014.3	4.800		02.87	12.00	T NONE
X	1	030.0	009.0	1.000		01.41	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	X	00003.06	24H-160F-

TOXICITY

05598 INSULATION FOAM LAST-A-FOAM POLYURETHANE FR3704 GID: CACQXX

MANF: GENERAL PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.500			05.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61849 INSULATION FOAM LAST-A-FOAM POLYURETHANE FR6709 GID: CACQXX

MANF: GENERAL PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	3.000		00.66	09.30	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

69938 INSULATION FOAM LS645C2

MANF: REPUBLIC PACKAGING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3			0.3	12.00	T NONE
I	1	030.0	010.0			0.4	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05698 INSULATION FOAM LUNAR F20 A/B EPOXY GID: CABGXX

MANF: LUNAR PRODUCTS INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.700			04.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.6E-6	5.52	.04		96H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	X	00007.16	96H-70F-

TOXICITY

62992 INSULATION FOAM MARTIN FRL3 5M GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.250		00.96	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60761 INSULATION FOAM MINICELL L200 FR GID: CACQXX

MANF: VOLTEK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	1.000			12.00	T LARGE
X	1	025.9	014.3	1.000		00.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.54	

TOXICITY

06576 INSULATION FOAM MINICELL L200 POLYETHYLN GID: CAEFXX

MANF: VOLTEK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	1.000		00.30	12.00	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005731 7

06576 INSULATION FOAM MINICELL L200 POLYETHYLN (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	1.000		00.70	11.90	T LARGE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.0E-6	4.49	.38	.15	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00021.83	

62175 INSULATION FOAM MINICELL L200/AL 5052H32 GID: CEXXXX

MANF: REPUBLIC PACKAGING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	3.125		00.00	00.00	NONE
A	1	025.9	014.3	3.325		00.00	00.00	NONE
A	1	033.0	014.3	3.125		00.00	00.00	NONE
A	1	033.0	014.3	3.325		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62169 INSULATION FOAM MINICELL L200/FLUOREL GID: ETCQXX

MANF: REPUBLIC PACKAGING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	1.100		00.18	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60954 INSULATION FOAM MINICELL L200/FREKOTE COATED GID: CACQXX

MANF: VOLTEK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	1.000		00.13	10.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85390 INSULATION FOAM MINICELL L200/REFSET RL 4389 COATING GID: CKXXXX

MANF: REPUBLIC PACKAGING/RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	24.5	14.5	1.00	0.062	00.02	12.0	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60364 INSULATION FOAM MISSELON POLYETHER GID: CAIEXX

....NO TEST DATA AVAILABLE....

20534 INSULATION FOAM MOLECULON FR302 POLYURETH GID: CACQXX

MANF: ILC DOVER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	3.500		00.06	11.80	T MOD
X	1	025.9	014.3	3.500		00.31	11.80	T MOD
X	1	030.0	009.0	0.700		00.21	09.80	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	6.2E-7	4.26	1.60		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00229.56	

61102 INSULATION FOAM MOLECULON RP11 URETHANE GID: FGXXXX

MANF: REISS INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	3.400		00.29	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	250.0	10	120	0.172	02	03
X	MECH	500	10	120	0.172	02	13

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00010.12	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005732 9

62993 INSULATION FOAM NCFI 22 65 GID: CAXXXX

MANF: NORTH CAROLINA FOAM

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.500			02.00	NONE	No test data	No test data							

62994 INSULATION FOAM NCFI 22 65 CONDENSATE GID: CAXXXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.500			02.30	NONE	No test data	No test data							

62995 INSULATION FOAM NCFI 22 65 MACHINED GID: CAXXXX

MANF: MARTIN MARIETTA

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.5	1.000	0.125		03.00	NONE	No test data	No test data							
A	1	030.0	014.5	1.000	0.125		03.70	NONE									
B	1	035.0	014.5	1.000	0.125		07.00	NONE									
I	1	040.0	014.5	1.000	0.125	00.30	12.00	T NONE									

62996 INSULATION FOAM NCFI 22 65 WET SPRAY GID: CAXXXX

MANF: MARTIN MARIETTA

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.375	0.125		01.30	NONE	No test data	No test data							
B	1	025.9	014.5	1.375	0.125		06.50	NONE									
I	1	030.0	014.5	1.375	0.125	01.50	12.00	T NONE									

62997 INSULATION FOAM NCFI 22 65 VANDENBERG GID: CAXXXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.500			01.50	NONE	No test data	No test data							

62998 INSULATION FOAM NCFI 22 65/FRL3 TY1 COATED GID: CAXXXX

MANF: MARTIN MARIETTA

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	030.0	014.5	1.000	0.125		05.50	NONE	No test data	No test data							
A	1	035.0	014.5	1.000	0.125		09.00	NONE									

65050 INSULATION FOAM NCFI 22-65 WITH FRL4 GID: CAXXXX

MANF: FABRIC RESEARCH LAB

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	015.0				02.75	NONE	No test data	No test data							
A	1	025.9	014.5				03.50	NONE									
B	1	030.0	014.5			00.09	07.37	NONE									

65224 INSULATION FOAM NCFI 23 38 MMC GID: CAXXXX

MANF: NORTH CAROLINA FOAM

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			01.54	NONE	No test data	No test data							

65225 INSULATION FOAM NCFI 23 58 POLYISOCYANURATE GID: CAXXXX

MANF: NORTH CAROLINA FOAM

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			05.58	NONE	No test data	No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005733 0

62999 INSULATION FOAM NCFI 25 13 GID: CAXXXX

MANF: MARTIN MARIETTA

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	2.300	0.100	00.00	00.00	NONE	No test data	No test data							

63000 INSULATION FOAM NCFI 25 13 RX6 GID: CAXXXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000	0.100		04.00	NONE	No test data	No test data							

63001 INSULATION FOAM NCFI 362 82 POLYURETHANE GID: CACQXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			03.60	NONE	No test data	No test data							

63002 INSULATION FOAM NCFI 367 POLYURETHANE GID: CACQXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			05.00	NONE	No test data	No test data							

63003 INSULATION FOAM NCFI 6A POLYISOCYANURATE GID: CAXXXX

MANF: MARTIN MARIETTA SPEC: NCFI-25-13

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			01.00	SMALL	No test data	No test data							

63004 INSULATION FOAM NCFI 7A POLYISOCYANURATE GID: CAXXXX

MANF: MARTIN MARIETTA SPEC: NCFI-25-13

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	2.900	0.100		03.00	NONE	No test data	No test data							

63059 INSULATION FOAM NCFI F11-A POLYURETHANE GID: CACQXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			03.90	NONE	No test data	No test data							

62390 INSULATION FOAM NEOPRENE LS200 GID: CADBXX

MANF: EXPANDED RUBBER

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.050			01.00	NONE	No test data	No test data							
A	1	030.0	010.0	0.050			00.20	NONE									

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
I	1.6E-6	1.38	.40	.09	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
	A 00022.17	

62096 INSULATION FOAM NEOPRENE NOC GID: CADBXX

MANF: DUPONT

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7				02.40	NONE	No test data	No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	14.58	5.24	.00	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005734 2

60325 INSULATION FOAM NOPCO N402-N-T/N-R GID: CADEXX

MANF: STEPAN CHEMICAL CO

....NO TEST DATA AVAILABLE....

61228 INSULATION FOAM NOPCO G306R/G306T GID: CADEXX

MANF: PPL-3226-78/8-79091
STEPAN CHEMICAL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.254		00.14	12.00	T MOD
X	1	025.9	014.3	0.254		00.66	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	6.3E-7	.73	.01		1H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00002.42	1H-150F-25.9% OXYGEN

61691 INSULATION FOAM NORYL FN215 GID: ETCHXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.252			00.10	NONE
A	1	023.8	014.5	0.252			00.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.1E-7	.32	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00020.11	

62535 INSULATION FOAM OMALON 1 FR/ACOUSTFAB LINER GID: ESCQCU

MANF: SCOTTFELD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.421			01.70	NONE
C	1	020.9	014.7	0.421			12.00	T SMALL
X	1	020.9	014.7	0.450		00.11	10.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62536 INSULATION FOAM OMALON 1 POLYURETHANE FR GID: ESCQXX

MANF: SCOTTFELD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.428		00.64	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61615 INSULATION FOAM OMALON 3 GID: CACQXX

MANF: CROFTON INC

SPEC: ST67F620-03

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.500		00.10	12.00	T MOD
X	1	025.9	014.3	0.500		01.05	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-5	3.85	.17		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.03	

62007 INSULATION FOAM OMAR100 POLYURETHANE GID: CACQXX

MANF: UNITED FOAM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	1.300		00.21	07.10	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63068 INSULATION FOAM PBO21-44 POLYURETHANE GID: CACQXX

MANF: POLYBLEND INC

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005735 4

63068 INSULATION FOAM PBO21-44 POLYURETHANE (cont)

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			04.30	NONE	No test data	No test data							

80064 INSULATION FOAM PDL 4034/OVERCOATED WITH SEA 200G SILICONE ELASTOMERIC ADHESIVE

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.250			00.10	NONE	No test data	No test data							

65231 INSULATION FOAM PDL/BX250 WITH CONATHANE GID: CACQXX

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			04.50	NONE	No test data	No test data							

65232 INSULATION FOAM PDL/BX250 WITH EPOXY PRIMER GID: CACQXX

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			03.50	NONE	No test data	No test data							

65230 INSULATION FOAM PDL/BX250 WITH TYBOND GID: CACQXX

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			04.41	NONE	No test data	No test data							

64328 INSULATION FOAM PDL4034 COVERED WITH L-T-80 TAPE AND THEN G401000 TAPE GID: CAXXXX

MANF: POLYMER DEVELOPMENT
SHELDAHL

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.500			01.10	SMALL	No test data	No test data							

06605 INSULATION FOAM PDL4034 FR POLYURETHANE GID: CACQXX

MANF: POLYMER DEVELOPMENT

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7	0.500			02.00	MOD	No test data	X	MECH	14.7	72	-297	0.250	2	05

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	20.47	

62955 INSULATION FOAM PDL4034 UNCOATED/MACHINED/IMBEDDED IN SHELL OF BX250 GID: CAXXXX

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	2.000	0.100		05.50	NONE	No test data	No test data							

63052 INSULATION FOAM PDL4034-12 UNCOATED WITHOUT SUBSTRATE GID: CAXXXX

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	2.000			06.00	NONE	No test data	No test data							

64304 INSULATION FOAM PDL4034-2.5 WRAPPED WITH ARAMID SLEEVING/COATED WITH PR1660/SEALED WITH DAPCOSEAL 2030

MANF: POLYMER DEVELOPMENT

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.600		00.04	00.50	NONE	No test data	No test data							
X	1	025.9	014.3	0.600		00.10	12.00	T MOD									

MSFC-HDBK-527 REV F 9999942 0005736 6

Information Handling Services, 2000

63051 INSULATION FOAM PDL4034-2.5/ SEALED WITH DAPCOSEAL 2030 GID: CAXXXX
MANF: MARTIN MARIETTA SPEC: STM-L-744

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7	1.100		01.23	06.50	NONE	No test data	No test data							
B	1	025.9	014.7	1.100		01.70	09.00	NONE									

64323 INSULATION FOAM PDL4034-2.5/COVERED WITH L-T-80 TAPE/SEALED WITH DAPCO 2030 GID: CAXXXX
MANF: D AIRCRAFT PRODUCTS

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.500			00.70	SMALL	No test data	No test data							

06039 INSULATION FOAM PDL4034-2.5S/ENSHROUDED IN METAL FOIL GID: CACQXX
MANF: POLYMER DEVELOPMENT SPEC: MB0130-149

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000		00.00	00.00	NONE	No test data	No test data							

05939 INSULATION FOAM PDL4034-2.5S/RL4389/TAPE GID: CAXXXX
MANF: SPEC: MB0130-149
....NO TEST DATA AVAILABLE....

60451 INSULATION FOAM PDL4034/COATED WITH FRL GID: CAXXXX
MANF: MARTIN MARIETTA SPEC: MB0125-078 MB0130-149
POLYMER DEVELOPMENT STM-L-744

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.100			05.50	NONE	No test data	No test data							
B	1	020.9	014.7	0.500		00.46	07.00	SMALL									
B	1	023.8	014.5	0.500		00.34	10.50	SMALL									
B	1	025.9	014.7	1.100			08.00	SMALL									
B	2	025.9	014.3	0.500			00.10	NONE									
B	1	025.9	014.3	0.500		00.20	06.50	SMALL									

63054 INSULATION FOAM PDL61 GID: CAXXXX
MANF: MARTIN MARIETTA SPEC: PDL 500-2.5

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			03.00	SMALL	No test data	No test data							

63055 INSULATION FOAM PDL62 GID: CAXXXX
MANF: MARTIN MARIETTA SPEC: PDL 500-2.5

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	2.000	0.100		06.00	NONE	No test data	No test data							

63062 INSULATION FOAM PELLETS FRL COATED GID: CAHSXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.437			05.00	NONE	No test data	No test data							

61332 INSULATION FOAM PHENEXPAN P40/P80 GID: ETBXXX
MANF: HUILES GOUDRONS&DERI

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
		023.8	014.5					NONE	No test data	No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005737 8

61332 INSULATION FOAM PHENEXPAN P40/P80 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.3E-6	9.38	.01		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

60796 INSULATION FOAM POLYCARBODIMIDE GID: ETMMXX

MANF: UPJOHN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	1.000			01.20	NONE
I	1	030.0	008.0	1.100		00.78	12.00	T NONE
I	1	040.0	008.0	1.100		02.29	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00001.75	24H-160F-

20752 INSULATION FOAM POLYCARBONATE 141/FLC95/BLK701 GID: CACAXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	2.000		00.02	03.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.23	.01		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00034.89	

60089 INSULATION FOAM POLYESTER OPEN CELL GID: CAXXXX

MANF: SCOTT AVIATION

....NO TEST DATA AVAILABLE....

62311 INSULATION FOAM POLYESTER/PVC FLAME BOND GID: CACBAE

MANF: STEPHENSON & LAWYER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.500		00.11	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	A 00019.32	

20754 INSULATION FOAM POLYETH L200/L3203-6 CTG

....NO TEST DATA AVAILABLE....

60765 INSULATION FOAM POLYETHER C190-39 GREEN GID: CACQXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	1.000		01.90	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.1E-6	1.16	.12	.55	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00020.46	72H-120F-

20419 INSULATION FOAM POLYETHER URETHANE RIGID GID: CECQXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	1.000		02.07	12.00	T NONE
X	1	030.0	009.0	0.800		01.32	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.0E-7	6.61	.00		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00005.04	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005738 T

60756 INSULATION FOAM POLYETHER/POLYURETHANE OPEN CELL GID: CCCQXX

MANF: SCOTT PAPER CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.15	.63	.21	48H-225F-0psiaVACUUM

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06603 INSULATION FOAM POLYETHYLENE ETHAFOAM 220 GID: CACFXX

MANF: DOW CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.380		00.11	12.00	T MOD
X	1	025.9	014.3	0.380		00.44	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.36	.08	.00	

ODOR

RT	RT WEIGHT	CURE
A	X 00021.99	

TOXICITY

60166 INSULATION FOAM POLYETHYLENE FLEXIBLE GID: CAXXXX

MANF: SPEC: PPP-C-1752

....NO TEST DATA AVAILABLE....

62990 INSULATION FOAM POLYETHYLENE FLEXIBLE GID: CAXXXX

MANF: DOW CHEMICAL SPEC: PPP-C-1752T1C2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	1.125		00.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	10.33	.00	:00	24H-70F-0psiaVACUUM

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64104 INSULATION FOAM POLYETHYLENE/EC2241 COAT GID: ESXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	1.000		00.02	12.00	MOD
X	1	030.0	010.0	1.000		00.01	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62294 INSULATION FOAM POLYIMIDE 1702 GID: CACDXX

MANF: SOLAR TURBINES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	2.100			00.10	NONE
A	1	030.0	009.0	2.100			01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	1.03	.00	.00	

ODOR

RT	RT WEIGHT	CURE
A	A 00002.69	

TOXICITY

06516 INSULATION FOAM POLYIMIDE 1720 GID: CACDXX

MANF: INTERNATIONAL HARVESTER
SOLAR TURBINES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.017			02.00	NONE
A	1	025.9	014.3	0.500			02.10	NONE
I	1	025.9	014.3	0.013		00.38	12.00	T NONE
A	1	030.0	009.0	2.200			02.10	NONE
I	1	033.0	014.3	2.000		00.35	10.00	T NONE
I	1	100.0	014.3	0.800		02.38	10.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005739 1

06516 INSULATION FOAM POLYIMIDE 1720 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.80	.00		

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	V	00006.85	

06620 INSULATION FOAM POLYIMIDE CHEMLON 701 GID: CCXXXX

MANF: CHEMTRONICS SPEC: JJ-8-37

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.005	0.003		01.40	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	2.2E-6	.95	.06	.73	SEE TEST REPORT

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	B	00015.50	SEE TST RPT

63063 INSULATION FOAM POLYIMIDE OPEN CELL 17021 GID: CCCDXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	1.000		00.00	00.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.92	.09	.00	16H-70F- 8H-140F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

65229 INSULATION FOAM POLYISOCYANURATE 1756 GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	015.0				04.83	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65219 INSULATION FOAM POLYISOCYANURATE 2380 GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7			00.09	10.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65223 INSULATION FOAM POLYISOCYANURATE 2381A GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7				03.75	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63073 INSULATION FOAM POLYISOCYANURATE 2382-P2B GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			02.30	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60192 INSULATION FOAM POLYISOCYANURATE 76-129 GID: CAXXXX

....NO TEST DATA AVAILABLE....

63064 INSULATION FOAM POLYISOCYANURATE FSC17A GID: CAXXXX

MANF: MARTIN MARIETTA SPEC: FSC 76-1-29

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			02.50	SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63065 INSULATION FOAM POLYISOCYANURATE FSC18A GID: CAXXXX

MANF: FOAM SYSTEMS SPEC: FSC 76-1-29

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	2.900	0.100	00.00	00.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0005740 8

Information Handling Services, 2000

63070 INSULATION FOAM POLYISOCYANURATE FSC55 GID: CAXXXX
MANF: FOAM SYSTEMS

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			04.70	NONE	No test data		No test data					

65226 INSULATION FOAM POLYISOCYANURATE FSC83A55 GID: CAXXXX

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7				04.21	NONE	No test data		No test data					

65220 INSULATION FOAM POLYISOCYANURATE FSC85A11 GID: CAXXXX
MANF: FOAM SYSTEMS

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			03.75	NONE	No test data		No test data					

65227 INSULATION FOAM POLYISOCYANURATE NCFI 23 66 GID: CAXXXX
MANF: NORTH CAROLINA FOAM

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7				03.42	NONE	No test data		No test data					
A	1	020.9	014.7	1.000	0.128	0.07	03.00	NONE								

65228 INSULATION FOAM POLYISOCYANURATE THR 251 GID: CAXXXX

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7				06.00	NONE	No test data		No test data					

60142 INSULATION FOAM POLYISOCYANURATE XR1002 GID: CAXXXX
MANF: GENERAL LATEX
....NO TEST DATA AVAILABLE....

63074 INSULATION FOAM POLYSTYRENE GID: CAHBXX

FLAMMABILITY										FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
I	2	020.9	016.2	0.125		00.01	05.00	T	NONE	No test data		No test data					
X	1	020.9	014.7	2.000			09.50		MOD								
X	1	020.9	014.7	1.000			05.00		MOD								
X	1	025.0	014.7	0.125			06.50		MOD								
I	1	027.0	014.7	0.125		00.07	12.00	T	NONE								
I	2	100.0	006.2	0.125		00.45	05.00	T	NONE								

THERMAL VACUUM STABILITY						ODOR		TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE	
A	1.0E-6	.50	.09	.00		No test data			

60080 INSULATION FOAM POLYSTYRENE LOW DENSITY FR GID: CAXXXX
MANF: SPEC: MIL-P-40619C2GA
....NO TEST DATA AVAILABLE....

63076 INSULATION FOAM POLYSTYRENE/FLOUROLUBE S30 COATED GID: CAHBXX

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			04.00	SMALL	No test data		No test data					
X	1	100.0	014.7	1.000		00.35	12.00	T MOD								

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005741 T

63075 INSULATION FOAM POLYSTYRENE/FLUORCHEM FC78 GID: CAHBXX

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7	1.000			04.70	MOD	No test data		No test data							

63077 INSULATION FOAM POLYSTYRENE/FR LATEX COATED GID: CAHBXX
MANF: MARTIN MARIETTA

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7	2.000			10.00	MOD	No test data		No test data							

63078 INSULATION FOAM POLYSTYRENE/HALOCARB OIL 1121 GID: CAHBXX

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			03.00	NONE	No test data		No test data							

63041 INSULATION FOAM POLYSTYRENE/HALOCARBON 6-25 COATED GID: CAHBXX
MANF: HALOCARBON PRODUCTS

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			03.50	SMALL	No test data		No test data							

63390 INSULATION FOAM POLYSTYRENE/HI VISC BFC FLUID GID: CAHBXX
MANF: HALOCARBON PRODUCTS
....NO TEST DATA AVAILABLE....

63042 INSULATION FOAM POLYSTYRENE/KEL-F 90 GREASE COATED GID: CAHBXX
MANF: 3M CO

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			03.00	NONE	No test data		No test data							
X	1	100.0	014.7	1.000		00.50	12.00	T MOD										

20259 INSULATION FOAM POLYURETHANE
MANF: FLAMEMASTER CORP SPEC: RB0130-087
FOAMEX POLY PROD
GENERAL ELECTRIC

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5			00.04	11.90	T MOD	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	1.0E-6	1.14	.00	.00	48H-212F-		V	00020.03	

63048 INSULATION FOAM POLYURETHANE GID: CACQXX

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7	1.000		00.18	07.00	NONE	No test data		No test data							

63058 INSULATION FOAM POLYURETHANE GID: CACQXX
MANF: LOCKHEED

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7	1.000		00.30	12.00	T MOD	No test data		No test data							

20492 INSULATION FOAM POLYURETHANE 2.7LB/CU FT
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005742 1

20572 INSULATION FOAM POLYURETHANE 3-4LBS SPEC: MIL-P-26514A

MANF:

....NO TEST DATA AVAILABLE....

64329 INSULATION FOAM POLYURETHANE 50150 GID: CAXXXX

MANF: FOAM CRAFT INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.800			02.30	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05215 INSULATION FOAM POLYURETHANE 711 GID: FJCQXX

MANF: COOK PAINT & VARNISH SPEC: MB0130-133T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	023.8	014.5	0.500		00.85	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.7E-6	12.93	.05		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20099 INSULATION FOAM POLYURETHANE A206 TR GID: CACQXX

....NO TEST DATA AVAILABLE....

63046 INSULATION FOAM POLYURETHANE AW420 GID: CACQXX

MANF: AMERICAN WESTERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			04.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80123 INSULATION FOAM POLYURETHANE ET

MANF: STEPAN CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7			00.30	10.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20118 INSULATION FOAM POLYURETHANE FLEXIBLE GID: CACQXX

MANF: ALL PLASTIC INC SPEC: MIL-P-26514T1

UPJOHN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			02.00	NONE
A	1	020.9	014.7	0.250			04.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.34	.43	.00	8H-257F-

ODOR

RT	RT WEIGHT	CURE
K	00020.03	

TOXICITY

63081 INSULATION FOAM POLYURETHANE FOA-1 GID: CCCQXX

MANF: ALLFORCE ACOUSTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	1.000			06.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63739 INSULATION FOAM POLYURETHANE FR GID: CAXXXX

MANF: 3M CO

M T I

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.250		00.10	7.25	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005743 3

63739 INSULATION FOAM POLYURETHANE FR (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00008.93	

05564 INSULATION FOAM POLYURETHANE FR6704/EC2241 4PCF GID: CACQDC
SPEC: MB0130-128T1
MANF: 3M CO
GENERAL PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.739		00.69	12.00	T NONE
I	1	023.8	014.5	0.700		00.91	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65222 INSULATION FOAM POLYURETHANE FS110 MMC GID: CADUXX
MANF: CULLERY CHEMICAL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	147.1	0.000			04.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63049 INSULATION FOAM POLYURETHANE FSC55 GID: CACQXX
MANF: FOAM SYSTEMS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			04.70	NONE
A	1	020.9	014.7	1.000			03.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63050 INSULATION FOAM POLYURETHANE FSC83A-55 GID: CACQXX
MANF: FOAM SYSTEMS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000		00.09	03.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63393 INSULATION FOAM POLYURETHANE FSC8BA55 P-2
MANF: TEXAS URETHANE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			03.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60948 INSULATION FOAM POLYURETHANE HR28 GID: CACQXX
MANF: SPEC: LAC23-4593

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.400		00.95	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00019.65	

63082 INSULATION FOAM POLYURETHANE HYFONIC 1 GID: CACQXX
MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	1.000			11.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00039.85	

MSFC-HDBK-527 REV F 9999942 0005744 5

Information Handling Services, 2000

63083 INSULATION FOAM POLYURETHANE ISOFOAM SS0658 GID: CACQXX

MANF: WITCO

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	2.000			03.50	NONE	No test data		No test data						

63057 INSULATION FOAM POLYURETHANE ISOFOAM SS0991 GID: CACQXX

MANF: WITCO

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7	1.000			09.50	NONE	No test data		No test data						

69804 INSULATION FOAM POLYURETHANE KIT FP60

MANF: INSTA-FOAM PROD

....NO TEST DATA AVAILABLE....

60265 INSULATION FOAM POLYURETHANE OPEN CELL GID: CCDUXX

MANF: SPEC: MIL-F-47254

....NO TEST DATA AVAILABLE....

65235 INSULATION FOAM POLYURETHANE P2004 GID: CACQXX

MANF: ISOTECH

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	015.0	0.500			05.30	NONE	No test data		No test data						

63072 INSULATION FOAM POLYURETHANE P2020 GID: CACQXX

MANF: ISOTECH

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			05.00	NONE	No test data		No test data						

63392 INSULATION FOAM POLYURETHANE P4

MANF: TEXAS URETHANE

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			04.30	NONE	No test data		No test data						

61978 INSULATION FOAM POLYURETHANE PDL2207 GID: CACQXX

MANF: POLYMER DEVELOPMENT

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	1.000		00.18	11.00	T MOD	No test data		No test data						
X	1	025.9	014.3	1.000		00.63	11.00	T MOD									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data						A	A	00007.84	

63067 INSULATION FOAM POLYURETHANE PDLX10-241 GID: CACQXX

MANF: POLYMER DEVELOPMENT

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			03.20	NONE	No test data		No test data						

63071 INSULATION FOAM POLYURETHANE PHR50 GID: CACQXX

MANF: URETHANE PRODUCTS

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7	1.000			06.30	NONE	No test data		No test data						

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005745 7

63391 INSULATION FOAM POLYURETHANE PQ2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			04.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80125 INSULATION FOAM POLYURETHANE S17-120B GID: CAXXXX

MANF: ISOCYANURATE PROD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.3				05.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63086 INSULATION FOAM POLYURETHANE SFP-237 GID: CACQXX

MANF: CALVARY CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	1.000			06.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62214 INSULATION FOAM POLYURETHANE STATHANE G502 SE GID: CACQXX

SPEC: HMS 16-1287T6F1

MANF: EXPANDED RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.27	.08	.00	6H-160F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63087 INSULATION FOAM POLYURETHANE TEXAS 407-22 GID: CACQXX

MANF: TEXAS URETHANE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			04.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63088 INSULATION FOAM POLYURETHANE UTAH 100-2-30F GID: CACQXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	1.000		00.15	06.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63089 INSULATION FOAM POLYURETHANE UTAH 320-315 GID: CACQXX

MANF: UTAH FOAM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			04.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20535 INSULATION FOAM POLYURETHANE VALSALVA GID: CACQXX

SPEC: CSD-SH-138

MANF: NASA/JSC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.700		00.31	06.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	X 00002.22	

TOXICITY

63080 INSULATION FOAM POLYURETHANE WITH COATING URETHANE GID: CACQXX

MANF: WITCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	2.500		00.04	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61793 INSULATION FOAM POLYURETHANE/AL TAPE L-T-80 GID: FDCQDE

SPEC: MB0135-133T2

MANF:

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005746 9

61793 INSULATION FOAM POLYURETHANE/AL TAPE L-T-80 (cont).

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	040.0	014.5	1.000		00.00	00.00	NONE	No test data		No test data							

05827 INSULATION FOAM POLYURETHANE/FABRIC/REFSET COAT GID: ETCQXX
MANF: ROCKWELL
SPEC: MB0120-043 MB0130-133T2
MB0130-136 MB0135-053

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	040.0	014.5	1.000		00.00	00.00	NONE	No test data		No test data							

63084 INSULATION FOAM POLYURETHANE/PLV 2000/SILICONE GID: CACQDP

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7				01.50	NONE	No test data		No test data							

63085 INSULATION FOAM POLYURETHANE/PLV 2000/WHT PAINT GID: CACQXX

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7			00.13	12.00	T MOD	No test data		No test data							

62117 INSULATION FOAM POLYURETHANE/POLYESTER 3013 GID: CACQCB
MANF: UNITED FOAM

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.800		00.15	12.00	T MOD	No test data		No test data							
X	1	025.9	014.3	0.800			12.00	T MOD										

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data						A	A	00020.07	

60763 INSULATION FOAM POLYURETHANE/TAPE AL 425 GID: ETCQXX
MANF: ROCKWELL

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000		00.00	00.00	NONE	No test data		No test data							

63229 INSULATION FOAM POLYURETHANE/TAPE AL 7402 GID: ETCQXX
MANF: ROCKWELL

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7	1.000	0.003	00.14	09.50	T MOD	No test data		No test data							

80138 INSULATION FOAM POUR EXP1 GID: CAXXXX
MANF: MMMA-MAF

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7				03.00	NONE	No test data		No test data							

85442 INSULATION FOAM POUR P2801 POLYISOCYANURATE GID: CKXXXX
MANF: GACO WESTERN INC

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000	0.125	00.09	03.00	NONE	No test data		No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005747 0

80137 INSULATION FOAM PUR EXP1 PANEL E

....NO TEST DATA AVAILABLE....

80014 INSULATION FOAM PYRELL GID: CAXXXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.900		0.10	00.90	NONE
X	1	030.0	010.0	0.900		1.30	12.10	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	2.69	.29	.29	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	22.245	

80020 INSULATION FOAM PYRELL ACOUSTICAL GID: CAXXXX

MANF: SCOTT PAPER CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
S

TOXICITY

RT	WEIGHT	CURE

61060 INSULATION FOAM PYRELL AFONIC ACCOUSTICAL POLYURETHANE GID: CACQXX

MANF: E N MURRAY COMPANY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	009.0	1.000		02.29	08.50	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00019.93	

63079 INSULATION FOAM PYRELL INSIDE BOX GID: CACQXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	1.000		00.56	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06010 INSULATION FOAM PYRELL LS645CX GID: CAXXXX

MANF: CUSTOM PACKING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	1.000			11.80	T SMALL
X	1	024.5	014.5	1.000			08.50	MOD
I	1	025.9	014.3	2.500			11.80	T SMALL
X	2	025.9	014.3	0.500		00.10	12.00	T MOD
X	1	025.9	014.3	0.500		00.40	12.00	T MOD
C	2	030.0	010.0	1.000		00.09	12.00	T SMALL
C	1	030.0	010.0	1.000		00.40	12.00	T NONE
I	1	040.0	008.0	1.000		00.52	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.6E-6	17.31	8.85		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00004.08	24H-160F-0psiaVACUUM

61533 INSULATION FOAM PYRELL PC210 COATING GID: CAHSXX

MANF: FIRE TECT
SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	025.9	014.3	1.000		00.00	00.00	NONE
A	1	025.9	014.3	1.000		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005748 2

61533 INSULATION FOAM PYRELL PC210 COATING (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	025.9	014.3	1.000		00.00	00.00	NONE
A	1	025.9	014.3	1.000		00.00	00.00	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

05733 INSULATION FOAM PYRELL UNCOATED GID: CACQXX

MANF: ESA
ESA/ERNO
SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	2.000			02.80	NONE
I	1	023.8	014.5	0.120		01.25	12.00 T	NONE
I	1	023.8	014.5	0.125		03.05	11.90 T	NONE
X	1	023.8	014.5	0.500		01.66	11.90 T	MOD
I	1	023.8	014.5	1.000		01.25	12.00 T	SMALL
B	2	024.5	014.5	0.400	0.080		05.00	NONE
B	1	024.5	014.5	0.400	0.080		11.00	NONE
B	2	024.5	014.5	0.375			05.00	NONE
B	1	024.5	014.5	0.375			11.00	NONE
X	1	024.5	014.5	0.500		00.25	12.00 T	NONE
X	1	025.9	014.3	0.203		01.32	12.00 T	MOD
X	1	025.9	014.3	1.100		01.07	12.00 T	MOD
X	2	025.9	014.3	0.500			00.80	MOD
X	1	025.9	014.3	0.500		00.46	12.00 T	MOD
C	2	025.9	014.3	1.000			01.10	NONE
C	1	025.9	014.3	1.000			08.70	NONE
I	2	025.9	014.3	5.000		01.02	22.40 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.26	.22	.15	24H-212F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00003.07	

20030 INSULATION FOAM PYRELL UNCOATED AND COATED RL4389 GID: CAXXXX

MANF: ESA
SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	1.000		00.25	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62359 INSULATION FOAM PYRELL WFP1406 CHARCOA GID: CACQXX

MANF: WILSHIRE FOAM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00067.27	

65504 INSULATION FOAM PYRELL WITH REFSET COATING GID: CAXXXX

MANF: SCOTT PAPER CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00192.05	

63718 INSULATION FOAM PYRELL/DC3140/UBS-N136 GID: CAXXXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	2.000		00.01	02.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005749 4

63718 INSULATION FOAM PYRELL/DC3140/UBS-M136 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	2.000		00.20	11.30	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00022.99	

61534 INSULATION FOAM PYRELL/FC273 COATING GID: CACQXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	2.020		02.04	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63090 INSULATION FOAM PYRELL/PLV2000 HS COATED GID: CACQXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.500			05.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61795 INSULATION FOAM PYRELL/PRESTO 765/UT GID: ESCQXX

MANF: PRESTO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	1.000		00.03	05.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
V	00007.01	

60518 INSULATION FOAM PYRELL/PRESTO P/6 GID: CAXXXX

MANF: PRESTO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	1.000		00.17	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.66	.35	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
V	00008.05	

63091 INSULATION FOAM PYRELL/REFSET RL4389 COATED GID: CACQXX

MANF: RAYBESTOS-MANHATTAN
SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.500			01.50	NONE
I	1	024.5	014.5	1.000		00.65	12.00	T NONE
I	1	025.9	014.3	0.500		00.11	11.80	T NONE
A	1	025.9	014.3	2.070			00.30	NONE
A	1	030.0	009.0	1.000			01.66	NONE
I	1	033.0	014.3	0.500		00.17	08.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
B	00192.05	2H-70F- 48H-125F-

61535 INSULATION FOAM PYRELL/RTV 3140 COATING GID: CACQXX

MANF: DOW CORNING
SCOTT PAPER CO

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005750 0

61535 INSULATION FOAM PYRELL/RTV 3140 COATING (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	1.000		00.09	12.00	T NONE
I	1	025.9	014.3	2.039		00.18	12.00	T NONE
I	1	030.0	010.0	2.700		00.09	11.70	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63093 INSULATION FOAM PYRELL/RTV 560 COATING GID: CACKXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	1.000			03.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00056.50	

69837 INSULATION FOAM PYROCUSHION NF300-18 GID: ESDUXX

MANF: SCOTFOAM CORPORATION

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	024.5	014.5	1.000		00.03	01.20	NONE
X	1	030.0	010.0	0.900			02.40	MOD
X	1	24.5	14.5	1.000		00.22	6.50	MOD
X	1	24.5	14.5	2.000		00.20	7.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

69836 INSULATION FOAM PYROCUSHION NF325-48 GID: ESDUXX

MANF: SCOTFOAM CORPORATION

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	1.000			05.70	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63094 INSULATION FOAM PYROTHANE GRADE 40/25 GID: CAXXXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	1.000			04.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00024.30	

63095 INSULATION FOAM PYROTHANE GRADE 45/35 GID: CAXXXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	1.000			03.00	NONE
C	2	025.9	014.3	1.000			00.10	NONE
C	1	025.9	014.3	1.000		00.40	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.43	

63096 INSULATION FOAM PYROTHANE GRADE 45/45 GID: CAXXXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	1.000			01.50	NONE
C	2	025.9	014.3	1.000			00.50	NONE
C	1	025.9	014.3	1.000		00.50	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005751 2

63096 INSULATION FOAM PYROTHANE GRADE 45/45 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00065.70	

TOXICITY

69846 INSULATION FOAM PYROTHANE LS GID: ESDUXX

MANF: SCOTFOAM CORPORATION

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	1.000			02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63097 INSULATION FOAM QUELFLAM SS624 GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.900	0.100		02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65293 INSULATION FOAM RENOLSOL RW54-02 GID: CADUXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7				05.12	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85441 INSULATION FOAM RS9412 POLYURETHANE GID: CKXXXX

MANF: STEPAN CHEMICAL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	1.000	0.062	00.20	12.0 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85408 INSULATION FOAM RS9412 POLYURETHANE REFSET RL4389 AND RTV 3140 COATED

MANF: STEPAN CHEMICAL CO/RAYBESTOS-MANHATTAN/DOW CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	1.000	0.062	00.04	05.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85440 INSULATION FOAM RS9412 WITH REFSET RL4389 FR COATED GID: CKXXXX

MANF: STEPAN CHEMICAL CO/RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	1.000	0.062	00.12	04.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80158 INSULATION FOAM SCOTT CUSTOM GRADE 80 PPI GID: CAXXXX

MANF: SCOTT PAPER CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	15.0	

TOXICITY

20244 INSULATION FOAM SCOTT FILTER PPI XX GID: CAXXXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.500		00.50	12.00 T	MOD
X	1	025.9	014.3	0.500		02.50	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.5E-6	1.73	.11	.23	

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.02	

TOXICITY

69809 INSULATION FOAM SCOTT INDUSTRIAL GID: CAXXXX

MANF: SCOTT PAPER CO

MSFC-HDBK-527 REV F 9999942 0005752 4

Information Handling Services, 2000

69809 INSULATION FOAM SCOTT INDUSTRIAL (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3			00.20	12.00	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	000024.2	

60625 INSULATION FOAM SCOTT S150-50 GRAY GID: CACQXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	1.000		03.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.1E-6	1.59	.25	.38	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.51	

61796 INSULATION FOAM SCOTTFELT 10-900 FR POLYURETHANE GID: ESCQXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.700			07.70	MOD
X	1	023.8	014.5	0.700		00.18	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00028.17	24H-160F-0psiaVACUUM

06277 INSULATION FOAM SCOTTFELT 3-900 FR POLYURETHANE GID: CACQXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	1.000			05.40	MOD
X	1	023.8	014.5	0.430		00.32	12.00	T MOD
X	1	023.8	014.5	0.425		00.16	12.00	T MOD
X	1	025.9	014.3	1.000		00.68	12.00	T MOD
X	2	025.9	014.3	0.520		00.09	08.70	MOD
X	1	025.9	014.3	0.520		00.38	12.00	T MOD
X	1	030.0	009.0	1.000		00.55	12.00	T MOD
X	2	030.0	010.0	0.800		00.10	08.20	MOD
X	1	030.0	010.0	0.800		00.80	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.9E-6	8.25	4.78	.19	24H-160F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00008.93	

63098 INSULATION FOAM SCOTTFELT GRADE 700ZH GID: CAXXXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	1.000			10.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00025.90	

65513 INSULATION FOAM SCOTTFELT INSULATION GID: CAXXXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.125		00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005753 6

65513 INSULATION FOAM SCOTTFELT INSULATION (cont)

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.125		00.80	12.00	T MOD									
X	1	030.0	010.0	0.125		00.80	12.00	T MOD									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	4.0E-6	10.87	5.65	.40		A	K	00021.17	

05013 INSULATION FOAM SILICONE RL1973 GID: CACKXX
MANF: RAYBESTOS-MANHATTAN

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	1.0E-6	2.79	.34			A	K	00018.12	

80095 INSULATION FOAM SILICONE RTF762/SF9650 GID: CACKXX
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	8.0E-6	1.52	.67	.01		No test data			

69801 INSULATION FOAM SILICONE RTV DC3-6548 GID: ABCKXX
MANF: DOW CORNING

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	1.0E-6	1.69	.33	.00		No test data			

20107 INSULATION FOAM SKYBOND POLYIMIDE GID: CACDXX
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

63101 INSULATION FOAM SLA561/FRL COATED/DMSO GEL GID: CAXXXX

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7	0.900			07.00	MOD	No test data		No test data						

60933 INSULATION FOAM SLATHANE 821-10 GID: CAXXXX
MANF: UPJOHN

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3			02.80	13.90	T MOD	No test data		No test data						

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	00448.34	

62321 INSULATION FOAM SOLIMIDE FF201 POLYIMIDE GID: CACBXX
MANF: I M I TECH CORP
INTERNATIONAL HARVESTER

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.0	088.0	1.200			02.70	SMALL	No test data		No test data						
A	1	030.0	010.4	1.200		00.00	00.00	NONE									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	1.0E-6	1.67	.01	.33		No test data			

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005754 8

62322 INSULATION FOAM SOLIMIDE TA301 POLYIMIDE GID: CACBXX

MANF: I M I TECH CORP
INTERNATIONAL HARVESTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.4	1.000		00.00	00.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	14.7	72	-297	0.250	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.05	.01	.47	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

80243 INSULATION FOAM SONEX 1 FR POROUS ACOUSTIC MELAMINE HYPALON COATED GID: CAXXXX

MANF: ILLBRUCK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	2.000			01.70	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

69952 INSULATION FOAM SONEX ACOUSTICAL FR GID: CAXXXX

MANF: ILLBRUCK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	3.400			00.50	NONE
C	1	020.9	014.7	3.400			12.00	T SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	22.347	

TOXICITY

61104 INSULATION FOAM STEPAN BX352 URETHANE GID: CACQXX

MANF: STEPAN CHEMICAL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.100			02.50	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
X	00003.71	

TOXICITY

62383 INSULATION FOAM STEPAN BX352M/DC3140 COATED GID: CAHSDP

MANF: STEPAN CHEMICAL CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00139.93	

TOXICITY

60918 INSULATION FOAM STEPAN BX352M/OCEAN CM987 GID: CAHSXX

MANF: STEPAN CHEMICAL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.250			09.40	SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
V	00163.93	

TOXICITY

63105 INSULATION FOAM STICK IU57/ALBICOTE FRL GID: CAXXXX

MANF: STANCHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.250			02.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005755 T

63108 INSULATION FOAM STICK IU57/HYPALON COATED GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.250		00.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63107 INSULATION FOAM STICK IU57/REFSET COATED GID: CAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.250		00.01	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62044 INSULATION FOAM STYRENE GID: CACMXX

MANF: DOW CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	1.000			05.70	MOD
X	1	100.0	014.7	1.000		60.00	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61757 INSULATION FOAM STYRENE 4486 GID: CACMXX

MANF: FOSTER GRANT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	1.000		00.65	12.00	T MOD
X	1	023.8	014.5	1.500			05.80	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00002.77	

61843 INSULATION FOAM STYRENE 5486 GID: CEHBXX

MANF: FOSTER GRANT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	1.400			05.20	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00002.69	24H-160F-0psiaVACUUM

61325 INSULATION FOAM STYROFOAM TG BLUE GID: CAXXXX

MANF: DOW CHEMICAL
DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.3	0.712			03.90	MOD
X	1	100.0	014.7	1.000		10.00	12.00	T MOD
X	1	100.0	012.3	0.713		03.02	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64962 INSULATION FOAM SYNTACTIC EPON 815 GID: BBBGXX

MANF: SHELL CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.500			00.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20313 INSULATION FOAM SYNTACTIC EPON 815/KEVLAR GID: BBBGJH

MANF: SHELL CHEMICAL SPEC: HP 16-108T1C4 HP 16-108T2C3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.514		00.04	11.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.12	.05	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005756 1

60750 INSULATION FOAM TEMPERFOAM C42 GID: ETXXXX

MANF: EDMONT WILSON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00019.98	

61125 INSULATION FOAM TEMPERFOAM T38 GID: CCCQXX

MANF: EDMONT WILSON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00009.79	

06389 INSULATION FOAM TEMPERFOAM T41 GID: CAXXXX

MANF: EDMONT WILSON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00007.44	

06388 INSULATION FOAM TEMPERFOAM T47 GID: CAXXXX

MANF: EXPANDED RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.57	.02	.17	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

61027 INSULATION FOAM TENNECO 6LBM BLACK GID: CAXXXX

MANF: TENNECO SPEC: MIL-P-26514E

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.2E-6	13.26	7.28	.30	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

65337 INSULATION FOAM TEST TUBE RACK 2610 GID: CACQXX

MANF: AMERICAN SCIENTIFIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	1.700		02.70	09.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00025.16	

60143 INSULATION FOAM TEXTHANE 2000-24 ISOCYANAU

MANF: TEXAS URETHANE

....NO TEST DATA AVAILABLE....

62003 INSULATION FOAM TEXTHANE 220-20 URETHANE GID: CACQXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	1.200			04.00	NONE
B	1	025.9	014.3	1.200			07.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.37	.00		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00019.83	

65234 INSULATION FOAM TEXTHANE 221-25 POLYURETHANE GID: CACQXX

MANF: TEXAS URETHANE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005757 3

65234 INSULATION FOAM TEXTHANE 221-25 POLYURETHANE (cont)

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	015.0	0.500			05.20	NONE	No test data	No test data						

60255 INSULATION FOAM TEXTHANE 333 GID: CKXXXX
MANF: UPJOHN
....NO TEST DATA AVAILABLE....

63109 INSULATION FOAM THERMOTROL 2122 POLYURETHANE GID: CACQXX
MANF: GENERAL ELECTRIC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
I	1	023.8	014.7	0.250		02.00	12.00 T	NONE	No test data	No test data						

62987 INSULATION FOAM TSR 3365 FR GID: CAXXXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.500			03.20	NONE	No test data	No test data						
A	1	020.9	014.7	0.250			05.30	NONE								

62984 INSULATION FOAM TSR336-2 FR GID: CAXXXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7	0.500		00.02	12.00 T	MOD	No test data	No test data						

62985 INSULATION FOAM TSR336-3 FR GID: CAXXXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.500			03.30	NONE	No test data	No test data						
I	1	020.9	014.7	0.250		00.07	12.00 T	NONE								

62986 INSULATION FOAM TSR336-4 FR GID: CAXXXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.500			03.60	NONE	No test data	No test data						
A	1	020.9	014.7	0.250			03.90	NONE								

63110 INSULATION FOAM TU2008-45-5 GID: CAXXXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.900	0.100		02.00	NONE	No test data	No test data						

63111 INSULATION FOAM TU2008-61-1 GID: CAXXXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	2.000	0.100		02.00	NONE	No test data	No test data						

63112 INSULATION FOAM TU28 URETHANE GID: CACQXX
MANF: MARTIN MARIETTA SPEC: TU-33X
TEXAS URETHANE

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			02.00	NONE	No test data	No test data						

63113 INSULATION FOAM TU32 URETHANE GID: CACQXX
MANF: MARTIN MARIETTA SPEC: TU-33X

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005758 5

63113 INSULATION FOAM TU32 URETHANE (cont)

MANF: TEXAS URETHANE

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	2.500	0.100		04.00	NONE	No test data		No test data							

62285 INSULATION FOAM TUFCOTE ACOUSTICAL GID: CAXXXX

MANF: SPECIALTY COMPOSITES

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.500		03.05	06.10	T MOD	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							V	00013.00	

62286 INSULATION FOAM TUFCOTE ACOUSTICAL 104 GID: CAXXXX

MANF: SPECIALTY COMPOSITES

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.796		01.37	07.50	T MOD	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	00020.16	

62735 INSULATION FOAM TUNNEL/ALBICOTE GID: CAXXXX

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7				01.50	NONE	No test data		No test data							

63106 INSULATION FOAM TX39 URETHANE GID: CACQXX

MANF: MARTIN MARIETTA SPEC: TX-2006-21B
TEXAS URETHANE

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000			03.00	NONE	No test data		No test data							

63115 INSULATION FOAM TX43 URETHANE GID: CACQXX

MANF: MARTIN MARIETTA SPEC: TX-2006-21B
TEXAS URETHANE

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	2.400	0.100		04.00	NONE	No test data		No test data							

63773 INSULATION FOAM UNICELLULAR POLYETHYLENE GID: CAXXXX

MANF: DOW CHEMICAL SPEC: PPP-C-1752 T1C2

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							X	00010.35	

62170 INSULATION FOAM URETH KUA100/FLUOREL COATED GID: CACQXX

MANF: CONSOLIDATED KINETIC

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	025.9	014.3	1.000		00.15	09.60	T NONE	No test data		No test data							
I	1	033.0	014.3	1.000		00.24	10.00	T SMALL										

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005759 7

60179 INSULATION FOAM URETHANE GID: CACQXX

MANF: TEXAS URETHANE SPEC: MIL-F-81254

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7			00.00	00.00	NONE
X	1	025.9	014.3	1.000		01.76	12.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.66	2.02	.00	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61532 INSULATION FOAM URETHANE BLACK GID: CACQXX

MANF: REPUBLIC PACKAGING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	1.000		00.69	12.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.69	.12	.00	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
A	00028.56	

TOXICITY

63529 INSULATION FOAM URETHANE CMHR GID: CACQXX

MANF: MOBAY CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.566		00.04	04.83	NONE
I	1	025.9	014.3	0.566		00.13	12.00	T NONE
I	1	025.9	014.3	4.000		00.43	12.00	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.5E-6	4.41	1.30	.44	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61770 INSULATION FOAM URETHANE FR G73C GID: ESCQXX

MANF: E R CARPENTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	1.000		00.25	12.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
A	V 00002.96	24H-160F-

TOXICITY

61756 INSULATION FOAM URETHANE FR Q31 GID: ESCQXX

MANF: E R CARPENTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	1.000		00.41	12.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
A	X 00004.23	24H-160F-

TOXICITY

61819 INSULATION FOAM URETHANE J52924 GID: CACQXX

MANF: CREST PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	1.000		00.40	12.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
A	B 00005.67	16H-160F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005760 3

62257 INSULATION FOAM URETHANE KUA GID: CACQXX

MANF: CONSOLIDATED KINETIC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	1.000		01.07	12.00	T MOD	No test data	No test data							

61817 INSULATION FOAM URETHANE KUA100U-7LF GID: CACQXX

MANF: CONSOLIDATED KINETIC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	023.8	014.5	1.000		01.49	12.00	T NONE	No test data	No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	V	00003.34	24H-160F-

61818 INSULATION FOAM URETHANE KUA50-7LF GID: CACQXX

MANF: CONSOLIDATED KINETIC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	0.500		00.67	11.90	T MOD	No test data	No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	V	00002.88	24H-160F-

61842 INSULATION FOAM URETHANE L200 GID: ETCQXX

MANF: REPUBLIC PACKAGING

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	3.400		00.41	12.10	T MOD	No test data	No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	X	00002.73	

80034 INSULATION FOAM URETHANE POROM CELLULAR FR GID: CACQXX

MANF: ROGERS CORP SPEC: P/N 4701-05-201-25-1637

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.120		00.05	12.0	T LARGE	No test data	No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.35	1.07	. 0	

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	K	48.0	

60932 INSULATION FOAM URETHANE R248E GID: CACQXX

MANF: STEPAN CHEMICAL CO

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	025.9	014.3	2.300		01.29	12.90	T NONE	No test data	No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	X	00009.50	

20298 INSULATION FOAM URETHANE SX136 GID: CACQXX

....NO TEST DATA AVAILABLE....

62253 INSULATION FOAM URETHANE/ARMALON/CSR300 ADHESIVE GID: CACQXX

MANF: REPUBLIC PACKAGING
SCOTT PAPER CO

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005761 5

63253 INSULATION FOAM URETHANE/ARMALON/CSR300 ADHESIVE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	1.000		00.08	11.10	T MOD

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00028.76	

62254 INSULATION FOAM URETHANE/BLACK VINYL COVER GID: CACQXX

MANF: SCOTT PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	1.000		00.56	10.90	T MOD

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62442 INSULATION FOAM URETHANE/LT80/REFSET COATED GID: CACSXX

MANF: ARROWHEAD PRODUCTS SPEC: MB0120-043 MB0135-133T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	040.0	014.5	1.500		00.00	00.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61862 INSULATION FOAM URETHANE/POLYETHER N GREY GID: °CCCOXX

MANF: SOUTHWEST KINETICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	1.000		00.47	12.00	T MOD

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00002.96	

62026 INSULATION FOAM URETHANE/PS ADHES GID: CABGCQ

MANF: CAMIE CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00003.32	

63116 INSULATION FOAM VONAR CLOTH BACKED TY 3 GID: CAXXXX

MANF: ALLEN INDUSTRIES INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.200			01.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62850 INSULATION FOAM WIPES MICRO-CLEAN POLYURETHANE GID: CACQXX

MANF: SCIENTIFIC ENTERPRISES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	14.7	72	-220		2	16

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.87	1.86	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

62788 INSULATION FOAM WITCO 658 FUTURA 5007/550 GID: AKCQMA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.060	0.003		01.50	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61841 INSULATION FOAM/KEVLAR PR1660/SEAL 2030 GID: FJJHXX

MANF: ROCKWELL SPEC: MB0120-065 MB0130-136

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005762 7

61841 INSULATION FOAM/KEVLAR PR1660/SEAL 2030 (cont)
MANF: SPEC: MBO130-149

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7				02.50	MOD	No test data		No test data							

62441 INSULATION FOAMGLAS CELLULAR GID: CAIAXX
MANF: PITTSBURG CORNING

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	2.000			00.10	NONE	No test data		No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR		TOXICITY	
RT	RT	WEIGHT	CURE
	A	00043.38	

61361 INSULATION FOMO FILL GID: CAXXXX
MANF: FOMO PRODUCTS

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.800		00.27	12.00	T MOD	No test data		No test data							
X	1	025.9	014.3	0.800		00.97	12.00	T MOD										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	21.84	.41	.00	

ODOR		TOXICITY	
RT	RT	WEIGHT	CURE
A	V	00019.28	24H-70F-

06334 INSULATION GLASS FAB/AL FOIL 104 GID: FJGDXX
MANF: SHELDAHL

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	2	020.9	014.7	0.003		00.00	00.00	NONE	No test data		No test data							
B	1	020.9	014.7	0.003			06.50	NONE										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.18	.05		

ODOR		TOXICITY	
RT	RT	WEIGHT	CURE
No test data			

03257 INSULATION GLASS FABRIC/ALUMINUM FOIL GID: FJGDXX
MANF: SPEC: MBO-065

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.37	.01	.00	

ODOR		TOXICITY	
RT	RT	WEIGHT	CURE
No test data			

06066 INSULATION GLASS WIRE IMPR. SYS T/C GID: FJGDXX
....NO TEST DATA AVAILABLE....

06588 INSULATION GLASS WOOL F100 GID: FJXXXX
MANF: ZIRCONIUM CORP
....NO TEST DATA AVAILABLE....

05739 INSULATION GLASS/NYLON RF1006-HS GID: FJGDXX
....NO TEST DATA AVAILABLE....

61845 INSULATION GLASS/PHENOLIC M-P-AA-W GID: CKIABX
MANF: HI TEMP INSULATION

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	023.8	014.5	0.600		00.02	12.00	T NONE	No test data		No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.2E-6	.53	.08		

ODOR		TOXICITY	
RT	RT	WEIGHT	CURE
No test data			

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005763 9

05625 INSULATION GLASS/PHENOLIC PEL05 GID: FJFVMD

MANF: OWENS CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.500		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	X 00001.32	

06422 INSULATION GLASS/RUBBER SIL-PAD 400 GID: FJGDXX

....NO TEST DATA AVAILABLE....

61032 INSULATION GLASS/SILICONE M-S-AA GID: FJCKIA

MANF: HI TEMP INSULATION SPEC: MB0135-024T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.518		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.1E-6	.50	.02	.14	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	K 00020.18	

20031 INSULATION ISOMICA CL20 INORGANIC GID: CKXXXX

MANF: 3M CO

....NO TEST DATA AVAILABLE....

60391 INSULATION JS220

....NO TEST DATA AVAILABLE....

06292 INSULATION KAOWOOL BULK A (INORG) GID: FJXXXX

MANF: BABCOCK & WILCOX

....NO TEST DATA AVAILABLE....

62424 INSULATION KAOWOOL CERAMIC/FOIL BACKING GID: FJHOFU

MANF: BABCOCK & WILCOX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	1.000		00.00	00.00	NONE
A	1	030.0	010.0	1.000			00.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62425 INSULATION KAOWOOL CERAMIC/SCRIM BK GID: FJHOFU

MANF: BABCOCK & WILCOX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	1.000		00.20	12.00 T	NONE
X	1	025.9	014.3	1.000		01.00	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

69957 INSULATION KAOWOOL CONSORT ATF FOIL

MANF: BABCOCK & WILCOX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	1.000		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 22.149	

69943 INSULATION KAOWOOL CONSORT ATF PLAIN

MANF: BABCOCK & WILCOX

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005764 0 ■

69943 INSULATION KAOWOOL CONSORT ATF PLAIN (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	1.000		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

02970 INSULATION LAMINATE K7023-1581 GID: COBGIA

MANF: U S POLYMERIC SPEC: MB0130-105T3C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.124			04.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.8E-7	.35	.01		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.23	

62561 INSULATION LAMINATE MARQUISETTE GID: CKCDHL

MANF: SHELDAHL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.36	.02		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

06376 INSULATION MATERIAL 550-02 QUARTZ FIBER GID: FJXXXX

MANF: AAI PRODUCTS SPEC: MB0135-082T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.300			01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.4E-6	.40	.00	.22	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

05921 INSULATION MICA BONDED GLASS INORG GID: CKXXXX

....NO TEST DATA AVAILABLE....

05186 INSULATION MICA MUSCOVITE GID: AZHFXX

MANF: MICA CORP SPEC: HH-I-536-TY-NMF

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.006		00.00	00.00	NONE
A	1	030.0	010.4	0.006		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.6E-6	.01	.01	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.05	

05032 INSULATION MICROLITE AA1 PHEN BIND GID: FJBXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.37	.15	.00	1H-500F- 4H-626F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

60230 INSULATION MSA-1

MANF: SPEC: P/N 10753-0001 USB-MS-1002

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.125	0.003		05.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60197 INSULATION MTA-1

MANF: AUGAT INC SPEC: USB-MS-2001

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005765 2

60227 INSULATION MTA-2
MANF: AUGAT INC SPEC: USB-MS-2003
....NO TEST DATA AVAILABLE....

61669 INSULATION MYLAR ALUMINIZED TYPE 2 GID: FJCBFJ
MANF: NATIONAL METALLIZING SPEC: ST92M059

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.001		00.93	12.00	T NONE
X	1	023.8	014.5	0.001		11.00	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.25	.03		

ODOR

RT	RT	WEIGHT	CURE
A	X	00000.55	

TOXICITY

61810 INSULATION NOMEX 410/KAP/LDR PAPER GID: CLBVXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	9.000			02.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61771 INSULATION PAPER ARMITE SLOT GID: FJGMXX
MANF: AQM SPEC: MIL-I-695

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.010		00.03	12.00	T SMALL
C	1	023.8	014.5	0.010		00.69	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05327 INSULATION PILE FIBROUS (INORGANIC) GID: FJXXXX
MANF: SPEC: MB0135-052
....NO TEST DATA AVAILABLE....

80251 INSULATION PIPE ARMAFLEX AP GID: CKXXXX
MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.554			03.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	10.37	5.34	.17	

ODOR

RT	RT	WEIGHT	CURE
A	V	22.012	

TOXICITY

05206 INSULATION PLENCO 1512 ALKYD/GLASS GID: FJAOIA
MANF: PLASTIC ENGINEERING SPEC: MC454-0066-0027

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.066			01.20	NONE
A	1	025.9	014.3	2.700	0.125		00.50	NONE
A	1	030.0	009.0	2.700	0.125	00.00	00.00	NONE
A	1	030.0	010.4				00.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.8E-7	1.48	.00		

ODOR

RT	RT	WEIGHT	CURE
	K	00019.81	

TOXICITY

60604 INSULATION POLYESTER FIBERMAT 2538 GID: DIXXXX
MANF: 3M CO SPEC: HMS 13-1696

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005766 4

60604 INSULATION POLYESTER FIBERMAT 2538 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.16	.02	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

63135 INSULATION POLYIMIDE/GLASS RI409/SLS21

MANF: DAINIPPON INK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.030			01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00070.70	

62086 INSULATION POLYSTYRENE/FLUOREL GID: FJHBDE

MANF: DOW CHEMICAL
RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	100.0	014.7	0.900		02.18	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61827 INSULATION POLYURETHANE SHEET 4050 GID: FJCQXX

MANF: GLOBAL CHEMICAL SYS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.023			02.20	SMALL
C	1	020.9	014.7	0.023		00.08	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06619 INSULATION POWDER S102/AL203 INORGANIC GID: CKXXXX

MANF: MCDANIEL REFRACTORY
....NO TEST DATA AVAILABLE....

62142 INSULATION PYRALUX POLYIMIDE GID: FJCDXX

MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.2E-7	.40	.02		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

63396 INSULATION RAPCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000		00.00	00.00	NONE
A	1	030.0	010.0	1.000			06.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20052 INSULATION REIN CARBON/CARBON GID: FJXXXX

MANF: LTV AEROSPACE CORP
....NO TEST DATA AVAILABLE....

20784 INSULATION REIN CARBON/CARBON/A-COATED

....NO TEST DATA AVAILABLE....

06507 INSULATION S102/SIC/AB312 GLZ (INORGANIC) GID: CKXXXX

SPEC: MB0115-032

MANF: LOCKHEED
....NO TEST DATA AVAILABLE....

05999 INSULATION SAFFIL ALUMINA HT MAT

SPEC: MB0135-067

MANF:
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005767 6

06070 INSULATION SIC IMR SIO2/GLAZE GID: FJXXXX
MANF: SPEC: MB0115-025
....NO TEST DATA AVAILABLE....

60480 INSULATION SILFRAY CERAMIC GID: CLXXXX
MANF: THERMAL MATERIALS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.05	.00		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61704 INSULATION SILICONE THERMAL GID: CKCKXX
MANF: HI TEMP INSULATION SPEC: MB0135-024

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.500		00.00	00.00	NONE
A	1	023.8	014.5	0.500			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	.23	.00		

ODOR

RT	RT WEIGHT	CURE
A	K 00004.85	

TOXICITY

62162 INSULATION SMRD 100F90 GID: FJXXXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.280		00.05	10.40	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.46	.29	.00	24H-212F- 110H-275F-0psiaVACUUM

ODOR

RT	RT WEIGHT	CURE
	V 00019.89	

TOXICITY

62164 INSULATION SMRD 100F90/FR 13 GID: FJXXXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.275		00.06	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	X 00019.86	

TOXICITY

62163 INSULATION SMRD 100F90/FR 7 GID: FJXXXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.273		00.06	10.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	X 00020.01	

TOXICITY

63484 INSULATION SOUND KNB5LR PVC/GL/PB GID: FJAEIA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.033		00.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.7E-6	5.38	3.63	.03	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

MSFC-HDBK-527 REV F 9999942 0005768 8

Information Handling Services, 2000

63771 INSULATION STYROFOAM GID: CKXXXX
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.62	.22	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00023.00	

63141 INSULATION STYROFOAM TG GID: CKXXXX
MANF: DOW CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	1.000			05.00	MOD
X	1	100.0	014.7	1.000		01.60	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63140 INSULATION STYROFOAM WHITE GID: CKXXXX
MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.937			06.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63142 INSULATION STYROFOAM/FRL COATED GID: CKXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.000			03.50	NONE
A	1	020.9	014.7	2.000			04.00	NONE
I	1	100.0	014.7	1.000		03.00	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61972 INSULATION STYROFOAM/STYRENE GID: CEHBXX
MANF: DOW CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.500		01.52	12.00 T	MOD
X	1	020.9	014.7	0.252			06.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	50	72	70	0.059	2	37
B	MECH	50	72	70	0.249	1	60

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.12	.07	.00	96H-250F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

63695 INSULATION TERMINAL 570-1994-XX0100 GID: BDXXXX
MANF: CAMBION

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00004.40	

61404 INSULATION TG15000/MYLAR/FEP TAPE GID: FJCKIA
MANF: 3M CO
HITCO
SHELDAHL

SPEC: MB0135-024 MB0135-047

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7				09.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61405 INSULATION TG15000/MYLAR/L-T-80 TAPE GID: FJCKFK
MANF: 3M CO

SPEC: MB0135-024T1C1 MB0135-02H
MB0135-047

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7				04.00	NONE
I	1	020.9	014.7			00.26	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005769 T

61403 INSULATION TG15000/SCOTCH 853 TAPE GID: DYCAXX
MANF: 3M CO SPEC: MB0135-024
HITCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.422		00.00	00.00	NONE
C	1	020.9	014.7	0.422		00.79	11.90 T	NONE
I	1	020.9	014.7	0.250		00.53	12.40 T	NONE

FSC: No test data

OXYGEN COMP: No test data

01018 INSULATION TG15000/SILICONE/GLASS BINDER GID: CKCKIA
MANF: HITCO SPEC: MB0135-024 MB0135-024T1
MB0135-024T2 MB0135-047
MB0135-047T4

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.288			00.40	NONE
A	1	020.9	014.7	0.353		00.00	00.00	NONE
A	1	025.0	008.0	0.500			00.82	NONE
A	1	025.0	008.0	0.548		00.00	00.00	NONE
A	1	025.9	014.3	1.200			00.80	NONE
A	1	025.9	014.3	0.280			00.80	NONE
A	1	030.0	009.0	1.200		00.00	00.00	NONE
A	1	030.0	009.0	0.280			00.70	NONE
A	1	033.0	014.3	1.200			00.80	NONE
I	1	035.0	008.0	0.500		00.10	09.00 T	NONE

FSC: No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	100	72	600	0.061	0	20
B	MECH	100	72	600	0.250	0	20
X	PNEU	1000		600	0.250	01	01
X	PNEU	1500		600	0.250	2	02
X	PNEU	500		600	0.060	2	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.12	.02	.00	48H-248F-0psiaVACUUM
C	2.0E-6	1.04	.16	.12	

ODOR: A

TOXICITY

RT	WEIGHT	CURE
X	00003.18	

61585 INSULATION TG15000/TI/TAPE 853/KAP GID: FJCDXX
MANF: 3M CO SPEC: MB0135-024 MB0135-047
SEE TEST REPORT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.935			02.20	NONE
A	1	020.9	014.7	1.200			04.60	NONE

FSC: No test data

OXYGEN COMP: No test data

80241 INSULATION THERMAL RI409/SLS 213B NOMEX GID: CKXXXX
MANF: DAINIPPON INK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	1.400			02.40	NONE

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY
No test data

ODOR: RT

TOXICITY

RT	WEIGHT	CURE
K	102.72	

60314 INSULATION THERMAL SILICA TAPE GID: CKXXXX
....NO TEST DATA AVAILABLE....

85471 INSULATION THERMAZIP 577 ALUMINIZED FIBERGLASS FABRIC WITH POLYIMIDE FOAM GID: CKXXXX
MANF: ACCESSIBLE PRODUCTS
....NO TEST DATA AVAILABLE....

61976 INSULATION URETHANE UNIFOAM S82M GID: FJDUXX
MANF: WILSHIRE FOAM SPEC: UL TYPE 94HF1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	1.000		00.12	12.00 T	MOD

FSC: No test data

OXYGEN COMP: No test data

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005770 6

61976 INSULATION URETHANE UNIFOAM S82N (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	1.000		00.60	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	11.34	5.35		24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00003.53	

63297 INSULATION WIRE CU/TFE/GL GID: EPHNCN

MANF: AQM SPEC: MIL-W-22759/12

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	4	020.9	014.7				08.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00154.10	

60649 INSULATION WIRE ESTANE 58202 GID: DLCQIE

MANF: B F GOODRICH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.08	

69855 INSULATION WIRE GREEN (PORTION FROM HYDROCARBON SAMPLE LINE)

MANF: NASA/KSC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.02	.01	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

20023 INSULATION WIRE POLYOLEFIN/KYNAR GID: EPCECJ

MANF: A E PETSCHE CO SPEC: MIL-W-81044/12

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3				00.10	NONE
X	1	025.9	014.3			00.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.5E-6	1.99	.13	.02	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00019.98	

65470 INSULATION WIRE SILICONE J-SIL39013 GID: EPXXXX

MANF: J-SIL SPEC: MC409-0014

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3			00.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

69854 INSULATION WIRE WHITE (PORTION FROM HYDROCARBON SAMPLE LINE)

MANF: NASA/KSC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.02	.02	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

61828 INSULATIOON POLYURETHANE SHEET 4070 GID: FJCQXX

MANF: GLOBAL CHEMICAL SYS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.032			00.20	NONE
X	1	020.9	014.7	0.032		00.20	09.60	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005771 8

20530 IRON OXIDE (INORGANIC)
MANF: AQM
....NO TEST DATA AVAILABLE....

30118 K-6 ALLOY TEST DISCS GID: CHEFXX
MANF: SIERRACIN/HARRISON
SPEC: M261-0033-0202, ME261-0033-0202, ME261-0033-0206, ME261-0033-0212, ME261-0033-206, ME261-0033T3, ME261-0033, ME261-0033-0204, ME261-0033-0208, ME261-0033-202, ME261-00330202

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1050	72	540	0.042	2	4
B	PNEU	1050		540	0.065	0	20
B	MECH	275	72	-297	0.047	0	20
B	MECH	275	72	-297	0.051	0	20
B	PNEU	4400		540	0.043	0	20
B	MECH	4400	72	540	0.043	0	20
B	MECH	550	72	70	0.050	0	20

60737 KEL-F 6060 GID: DMXXXX
MANF: FLUOROCARBON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1675	72	70	0.062	00	20
Z	MECH	2500	72	70	0.060	01	23
C	MECH	5000	20	70	0.062	0	20

62504 KEL-F 6061-T6 10% GLASS GID: DKMAFV
MANF: FLUOROCARBON CORP
SPEC: AMS 3646

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.005	0	40
I	MECH	44	72	400	0.144	0	20

06197 KEL-F 800 MEK/SPRAY GID: ABEFXX
MANF: 3M CO
DUPONT
TD-RT
SPEC: MB0130-154, ST41F392-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002			05.20	NONE
A	1	020.9	014.7	0.003			06.00	NONE
A	1	023.8	014.5	0.011	0.003		01.00	NONE
A	1	025.9	014.3	0.001	0.003		00.80	NONE
A	1	100.0	020.2	0.001	0.003		01.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	2.0E-6	.56	.02		24H-70F- 24H-70F-

ODOR

RT	WEIGHT	CURE
B	00023.27	2H-70F-AFTER ONE BRUSH COAT WAS APPLIED. 24H-70F-A SECOND BRUST COAT WAS APPLIED OVER THE FIRST CURED COAT. 24H-150F- 720H-70F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005772 T

05521 KEL-F 81 GID: CHBFXX

MANF: 3M CO
AEROMAT PLASTICS
AFTON PLASTICS
AIR-LOCK INC
CADILLAC PLASTICS
CARLETON CONTROLS
CHEMPLAST
FLUOROCARBON CORP
GROVE VALVE & REGULATOR
NORDIC
POLYFLON CORP
PORT PLASTICS
TESCOM CORP
THERMECH ENGINEERING

SPEC: AMS 3646
AMS 3650A
MIL-P-46036T1
MIL-P-55028G3
AMS 3650
MIL-P-46036
MIL-P-46036T2
P.O. 98365

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME
A	AMMONIA
A	HYZE
A	MMH
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		250	0.061	2	06
X	PNEU	1000		350	0.055	2	15
B	PNEU	1000		70	0.051	0	20
B	PNEU	1000		70	0.060	0	20
B	PNEU	1000		70	0.060	0	40
B	MECH	1000	72	70	0.060	0	20
X	PNEU	1000		70	0.060	2	22
A	MECH	1050	72	70	0.060	0	40
A	MECH	1050	72	70	0.070	2	328
B	MECH	1050	72	70	0.088	0	20
A	MECH	14.7	72	-297	0.060	00	60
B	MECH	14.7	72	-297	0.125	0	20
X	PNEU	14.7		-297	0.230	01	20
X	MECH	1500	10	-297	0.060	01	17
B	PNEU	1500		70	0.031	0	20
X	PNEU	1500		70	0.060	2	42
C	MECH	2000	72	70	0.049	02	08
X	PNEU	2000		70	0.060	7	48
C	MECH	2500	72	70	0.049	1	15
B	PNEU	2500		70	0.060	0	40
B	PNEU	255		275	0.060	0	20
B	MECH	255	72	275	0.060	0	20
C	MECH	3000	72	70	0.033	1	2
C	MECH	3000	25	70	0.060	00	20
X	PNEU	3000		70	0.060	5	100
X	PNEU	3300		250	0.060	08	09
X	MECH	3300	10	250	0.060	0	20
X	PNEU	3500		70	0.060	5	24
X	PNEU	3500		70	0.060	5	56
B	MECH	4000	40	-297	0.060	00	20
C	MECH	4000	30	70	0.060	00	20
X	PNEU	4000		70	0.060	7	45
X	PNEU	4500		70	0.060	3	28
B	PNEU	500		70	0.035	0	20
B	PNEU	500		70	0.060	0	40
Z	MECH	5000	72	70	0.049	2	02
X	PNEU	5000		70	0.060	4	48
X	PNEU	5500		70	0.060	2	49
C	MECH	6000	40	70	0.033	0	20
X	PNEU	6000		70	0.060	2	46

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005773 1

05521 KEL-F 81 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	6000	20	70	0.060	0	20
X	PNEU	6500		70	0.060	1	08
X	PNEU	7000		70	0.060	02	02
X	PNEU	7000		70	0.060	2	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.03	.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61590 KEL-F 81 EXPANDED/BLUE BEADING GID: DDBFXX

MANF: CHEMPLAST

SPEC: AMS 3650A

FLAMMABILITY

No test data

FSC

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	20	-297	0.054	0	20

61648 KEL-F 81 PV 506 GASKET GID: CHBFXX

MANF: 3M CO

SPEC: AMS 3650A

FLAMMABILITY

No test data

FSC

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	2000		70	0.250	0	20
X	PNEU	2500		70	0.250	3	84
X	PNEU	4000		70	0.250	2	06
X	MECH	4000	72	70	0.350	0	01
X	PNEU	5000		70	0.250	3	32
B	MECH	5000	72	70	0.350	0	20
Z	MECH	5500	72	70	0.350	2	7
X	PNEU	6000		70	0.250	01	01
C	MECH	6000	72	70	0.350	1	2

65533 KEL-F 81/6060 RESIN GID: CHBFXX

MANF: FLUOROCARBON CORP

FLAMMABILITY

No test data

FSC

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	4500		75	0.060	02	02
B	MECH	6000	72	70	0.250	00	20

65472 KEL-F 81/6061 RESIN GID: CHBFXX

MANF: 3M CO
FLUOROCARBON CORP

FLAMMABILITY

No test data

FSC

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.010	00	20

65095 KEL-F 81/AR-7

FLAMMABILITY

No test data

FSC

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	14.7	30	-297	0.070	0	20
B	PNEU	1500		70	0.070	0	20
X	MECH	4000	15	-297	0.070	1	12
X	MECH	4000	15	70	0.070	1	03

05084 KEL-F CTFE UNPLASTICIZED GID: DKBDBD

MANF: 3M CO
A M PLASTICS
AFTON PLASTICS

SPEC: AMS 360
AMS 3649
AMS 3654
AMS 3645
AMS 3650
MC284-0395

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005774 3

05084 KEL-F CTFE UNPLASTICIZED (cont)

MANF: AMP INC
AQM
CADILLAC PLASTICS
CONSOLIDATED CONTROLS
DRAGON VALVES INC
FLUOROCARBON CORP
PLASTIC PROFILE
POLYFLON CORP
THERMECH ENGINEERING

SPEC: MIL-P-46036 MIL-P-46036T1
MR4244-PO713074 RBO130-094 CE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.3	0.008			00.20	NONE
A	1	023.8	014.3	0.008			00.20	NONE
A	1	024.5	014.3	0.008			00.20	NONE
A	1	025.9	014.3	0.008			00.20	NONE
A	1	030.0	010.0	0.008			00.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		250	.060	3	50
X	PNEU	1000		250	0.060	3	50
X	MECH	1000	10	250	0.060	0	20
B	PNEU	1000		70		0	20
B	MECH	1050	72	250	0.006	0	20
B	MECH	1050	72	69	0.088	0	20
B	PNEU	1250		200	.030	0	20
B	PNEU	1250		200	0.030	0	20
Z	MECH	1250	72	250	0.030	2	10
B	MECH	14.7	35	-297	0.006	0	20
B	MECH	14.7	65	-297	0.010	0	20
A	MECH	14.7	72	-297	0.060	0	20
A	MECH	15	72	70	0.020	0	20
B	MECH	150	72	275	0.040	0	20
B	PNEU	1500		70	0.060	0	20
A	MECH	200	72	-297	0.050	0	20
X	PNEU	2000		70	0.060	4	18
C	MECH	2500	60	70	0.064	0	20
B	MECH	260	72	200	0.088	1	57
B	MECH	260	72	250	0.005	0	20
X	PNEU	3300		250	0.060	14	21
X	MECH	3300	10	250	0.064	0	20
X	PNEU	3500		70	0.060	1	04
C	MECH	3700	25	69	0.070	0	20
A	MECH	400	72	-297	0.040	0	60
A	MECH	400	72	-297	0.088	0	60
A	MECH	50	72	-297	0.051	0	20
B	PNEU	500		70	0.020	0	40
C	MECH	6000	30	70	0.060	0	20
B	PNEU	9000		70	0.034	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.03	.01	00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00022.08	

05421 KEL-F FR-86J BETA GID: CHXXXX

....NO TEST DATA AVAILABLE....

60452 KEL-F PLASTICIZED GID: CHEFXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	009.0	0.068			00.40	NONE
A	1	023.8	009.0	0.068			00.40	NONE
A	1	024.5	009.0	0.068			00.40	NONE
A	1	025.9	009.0	0.068			00.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	1050	72	70	0.088	0	20
X	PNEU	2000		70	0.061	3	36
X	PNEU	3500		70	0.061	2	23
Z	MECH	3750	72	70	0.088	02	07

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005775 5

60452 KEL-F PLASTICIZED (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.068			00.40	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	4500		70	0.061	2	08
X	MECH	5500	10	70	0.060	0	20
X	PNEU	5500		70	0.061	2	13
X	PNEU	6500		70		4	41

60904 KEYBOARD COMPUTERWISE TT1A GID: FCXXXX
MANF: TRANSTEAM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	01106.40	

64097 KIT FLIGHT EXPERIMENT CARRY-ON GID: EXXXXX
MANF: HUGHES AIRCRAFT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	05599.00	

61030 KNEEBOARD ASSEMBLY WITH MECHANICAL PENCIL GID: FCXXXX
MANF: SAFETECH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00461.45	

20609 KNIFE SWISS ARMY 136KMAU GID: DDMDBX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00104.01	

06496 KRATON 2701 MANIFOLD FITTING
....NO TEST DATA AVAILABLE....

61764 KYNAR 460
MANF: PENNWALT CORP
WESTLAKE PLASTICS CO

SPEC: ME276-0032

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE
X	HYZE
A	MMH
A	N204

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	600	25	130	0.016	0	20
X	MECH	600	10	350	0.070	0	20
X	PNEU	650		350	0.070	2	10
X	PNEU	650		500	0.055	2	03
X	MECH	650	10	500	0.066	01	07

80067 KYNAR 740
MANF: WESTLAKE PLASTICS CO

SPEC: MC276-0032

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	600	40	130	0.020	00	120

06412 KYNAR MELTABLE PIGMENTED BLUE GID: CHDFXX
MANF: RAYCHEM CORP

SPEC: ME416-0031

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.56	

MSFC-HDBK-527 REV F 9999942 0005776 7

Information Handling Services, 2000

06413 KYNAR MELTABLE PIGMENTED RED GID: CHDFXX
MANF: RAYCHEM CORP SPEC: ME416-0031

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.36	

06414 KYNAR MELTABLE PIGMENTED YELLOW GID: CHDFXX
MANF: RAYCHEM CORP SPEC: ME416-0031

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.50	

05838 KYNAR PLASTIC FLUORIDE GID: EHCTXX
MANF: CADILLAC PLASTICS
PENNWALT CORP
WESTLAKE PLASTICS CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	650	72	70	0.021	0	20
X	MECH	650	10	70	0.060	0	20
B	PNEU	650		70	0.062	0	20

80049 LABEL 71-6165 ALUMINIZED SIGHTING WITH PS ADHES GID: CNFJXX
MANF: KEUFFEL & ESSER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
S								NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.35	.04	.07	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

80127 LABEL 721 POLYESTER FILM WITH B196 PS ADHES
MANF: BRUNSON INSTRUMENT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.007	0.003		01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	1.52	.19	.22	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

60495 LABEL 7720/7710/7920/ADHESI 'E 400 GID: CNXXXX
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00004.26	

65456 LABEL 8060 PLASTIC/POLYESTER BASE GID: CNXXXX
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00009.68	

65078 LABEL 8084-YG REMOVABLE GID: CNBGXX
MANF: AVERY INTERNATIONAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00022.44	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005777 9

80282 LABEL BAR CODE ACRYLIC

MANF: METAL CRAFT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.011	0.003	00.12	05.50	MOD
A	1	025.9	014.3	0.074	0.064	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.0E-6	.63	.03	.15	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

85435 LABEL CAUTION FLEXCON MYLAR WITH ACRYLIC PS ADHESIVE V23 WITH HAZDAR MY111 BLACK AND PANTONE 803C FLUORESCENT GID: CNXXXX

MANF: BORDEN DECAL CO SPEC: P/N LS41567-001

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.004	0.003	00.38	13.0	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61386 LABEL GRAVOFLEX GID: CNBYXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.036		00.05	12.00	T MOD
X	1	025.9	014.3	0.036		00.30	11.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00015.95	

TOXICITY

62736 LABEL IDENTIFICATION GID: CMXXXX

MANF: TELEDYNE BROWN ENG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	024.5	014.5	0.034			00.10	MOD
X	1	024.5	014.5	0.034		00.56	10.20	NONE
I	1	030.0	010.0	0.034		00.35	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63663 LABEL IDENTIFICATION GID: DIXXXX

MANF: TELEDYNE BROWN ENG

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00210.00	

TOXICITY

20382 LABEL IDENTIFICATION 126 FABRIC GID: CNBFXX

MANF: C & R SILK SCREEN SPEC: ST11L127-03

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.011		01.85	07.40	T NONE
I	1	100.0	020.2	0.011		07.40	07.40	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	9.0E-7	.90	.08		

ODOR

RT	RT WEIGHT	CURE
X	00003.55	

TOXICITY

20100 LABEL IDENTIFICATION ALUMINUM FOIL PS MC1960010 GID: FPFKXX

....NO TEST DATA AVAILABLE....

05238 LABEL IDENTIFICATION ALUMINUM FOIL/PS ADHESIVE 467 GID: CNXXXX

MANF: SPEC: MIL-P-19834T1

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005778 0

05193 LABEL IDENTIFICATION ASSEMBLY ACRYLIC ADHESIVE/AL GID: CNXXXX
SPEC: MB0190-001
MANF:
....NO TEST DATA AVAILABLE....

85422 LABEL IDENTIFICATION FLEXOFILM CHROME MYLAR WITH NAZDAR MY111 BLACK INK WITH ACRYLIC PS V23 ADHESIVE GID: CNXXXX
MANF: FLEXOFILM
SPEC: P/N LS40554-001 P/N LS40554-003
P/N LS40572-001 P/N LS40572-003

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.060		00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	19.82	

85444 LABEL IDENTIFICATION FLEXOFILM ACRYLIC PS ADHESIVE V23 WITH NAZDAR MY111 BLACK AND MY124 ORANGE INK
MANF: BORDEN DECAL CO
SPEC: P/N LS41533-001 P/N LS41533-002

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.060		00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20660 LABEL IDENTIFICATION ILC UNSPRAYED NOT TYPED GID: CNXXXX
MANF: C & R SILK SCREEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.011		01.54	12.30	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.6E-6	1.56	.04		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00005.10	

02257 LABEL IDENTIFICATION MARKING FOIL TFE GID: CNCNXX
MANF: KINGSLEY MACHINE CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.001		01.60	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00018.29	

61524 LABEL IDENTIFICATION MYLAR ADHESIVE 850 CLEAR GID: CNCCXX
MANF: 3M CO
SPEC: AB0190-004 T2 MIL-P-38477

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002	0.003		04.80	NONE
B	1	025.9	014.3	0.002	0.003	00.30	07.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.2E-6	.44	.04	.20	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00016.76	

61525 LABEL IDENTIFICATION MYLAR ADHESIVE 850/RED GID: CNCCXX
MANF: 3M CO
SPEC: AB0190-004 T2 MIL-P-38477

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002	0.003	00.58	06.10	NONE
B	1	025.9	014.3	0.002	0.003	00.31	08.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.2E-6	.65	.02		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.86	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005779 2

61526 LABEL IDENTIFICATION MYLAR ADHESIVE 850/SILVER GID: CNCCXX

MANF: 3M CO — SPEC: AB0190-004 T2 — MIL-P-38477

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002	0.003		04.60	NONE
A	1	025.9	014.3	0.002	0.003		05.50	NONE
B	1	030.0	009.0	0.002	0.003	00.50	06.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.2E-6	.55	.00		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00018.52	

05682 LABEL IDENTIFICATION MYLAR ADHESIVE 853/CLEAR GID: CNCCXX

MANF: 3M CO — SPEC: AB0190-004 T2 — MIL-P-38477

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002	0.003		05.50	NONE
B	1	025.9	014.3	0.002	0.003	00.26	07.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.2E-6	1.11	.00	.29	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00019.96	

05311 LABEL IDENTIFICATION MYLAR/ALUMINUM ST66D28-1 GID: DYCCFK

MANF: MARKEM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.8E-7	.65	.05		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
No test data		

61966 LABEL IDENTIFICATION PAPER DOTS GREEN GID: CNXXXX

MANF: FRALOCK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.0E-6	3.05	.47		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
No test data		

20890 LABEL IDENTIFICATION POLYESTER/RAYON

....NO TEST DATA AVAILABLE....

62068 LABEL IDENTIFICATION PVC/CLOTH STREAMER GID: BFAEXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.009		01.47	18.10	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

69985 LABEL IDENTIFICATION SCOTCHCAL 8006 RED/TRANSPARENT GID: CNXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	032.0	010.0	0.003	0.003		05.90	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	7.636	

06537 LABEL IDENTIFICATION SCOTCHCLAD 8005 ADHESIVE/ALUMINUM

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.61	.03	1.05	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00023.66	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005780 9

06033 LABEL IDENTIFICATION TEMPILABEL BE2XXF GID: CNXXXX

MANF: BIG 3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.010	0.003	00.48	06.20	T MOD
X	1	030.0	009.0	0.010	0.003	00.56	06.30	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20688 LABEL IDENTIFICATION UCD CLIPS 0109-22061-01 GID: FCXXXX

MANF: GSA

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.48	.12	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00011.14	

61189 LABEL KRYLON ACRYLIC SPRAY-ON GID: ASAKXX

SPEC: ST11L895-01 ST40A859-01

MANF: BORDEN
C & R SILK SCREEN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00004.23	

60995 LABEL LETRALINE #11 GID: CNXXXX

MANF: LETRASET USA INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.006	0.003	00.20	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	3.99	.46	1.77	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.12	

62017 LABEL MARKING RC 55 PAPER GID: CNXXXX

MANF: EASTMAN KODAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.36	2.12	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00007.93	

64102 LABEL METALPHOTO GID: DTGIXX

SPEC: MIL-P-15024

MANF: METALPHOTO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00022.95	

62470 LABEL NOMEX/RAYON GID: CNBVXX

MANF: KLOPMAN MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.051		00.31	06.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00012.47	

20709 LABEL PAPER JCP-E20

....NO TEST DATA AVAILABLE....

65361 LABEL STOWAGE LOCATION DES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00010.47	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005781 0

62365 LABEL TEMPILABEL 4D-150/66 GID: CNXXXX
MANF: TEMPIL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	3.63	.65	1.18	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62364 LABEL TEMPILABEL 8D-210/99 GID: CNXXXX
MANF: TEMPIL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	1.64	.44	.33	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

69882 LABEL ULTRACOLOR 00093 KHAKI GID: CNXXXX
MANF: METALPHOTO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	21.43	

TOXICITY

69886 LABEL ULTRACOLOR 17210 BLACK GID: CNXXXX
MANF: METALPHOTO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	21.80	

TOXICITY

69885 LABEL ULTRACOLOR 17214 BROWN GID: CNXXXX
MANF: METALPHOTO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	21.92	

TOXICITY

69883 LABEL ULTRACOLOR 17215 PURPLE GID: CNXXXX
MANF: METALPHOTO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	21.69	

TOXICITY

69880 LABEL ULTRACOLOR 17218 GREEN GID: CNXXXX
MANF: METALPHOTO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	21.88	

TOXICITY

69881 LABEL ULTRACOLOR 17219 YELLOW GID: CNXXXX
MANF: METALPHOTO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	21.79	

TOXICITY

69884 LABEL ULTRACOLOR 17220 ORANGE GID: CNXXXX
MANF: METALPHOTO CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	21.70	

TOXICITY

69953 LABELS BRADY 684 TEFLON
MANF: W H BRADY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.010			03.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0005782 2

Information Handling Services, 2000

69951 LABELS BRADY XB652 HIGH TEMPERATURE

MANF: W H BRADY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.005	0.003		02.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	10.585	

63876 LABELS PAPER P/S GID: DIXXXX

MANF: GSA

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00004.28	

69877 LABELS PRES-A-PLY REMOVABLE GID: CNXXXX

MANF: DINNISON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.004	0.003	0.50	11.70	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	5.33	

80303 LABELS THERMOFIT SLIP-ON HT TMS CM

MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.050		00.05	05.75	LARGE
A	1	025.9	014.3	0.50		00.03	01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	37.0	

85399 LABELS THERMOFIT TIE-ON HT TMS CM GID: CNXXXX

MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	25.9	14.3	0.023		00.07	05.50	NONE
B	1	30.0	09.0	0.023		00.04	06.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	25.3	

85497 LACING CORD GUDEBROD DPT-H DACRON

MANF: GUDEBROD BROS SILK

....NO TEST DATA AVAILABLE....

20316 LACING CORD KEVLAR GID: EUJHXX

MANF: BENTLEY HARRIS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.011			03.50	NONE
A	1	025.9	014.3	0.084			03.00	NONE
X	1	025.9	014.3			00.20	11.70	T MOD
C	2	033.0	014.3	0.084			01.00	NONE
C	1	033.0	014.3	0.084		00.25	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005783 4

20316 LACING CORD KEVLAR (cont)

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.3E-6	3.05	.05			A	V 00020.10	

61794 LACING TAPE 217 GID: ECXXXX
MANF: AIRTEX SPEC: MIL-T-43435

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	0.010		02.03	07.70	MOD	No test data	No test data							

60791 LACING TAPE 615-158-1 GID: ECBVDE
MANF: FABRIC RESEARCH LAB

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.4E-6	2.12	.03			No test data		

60789 LACING TAPE 615-158-3 GID: ECBVDE
MANF: FABRIC RESEARCH LAB

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.4E-6	1.77	.05			No test data		

60790 LACING TAPE 615-158-5 GID: ECBVDE
MANF: FABRIC RESEARCH LAB

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.4E-6	3.23	.06			No test data		

63167 LACING TAPE A050 GID: ECXXXX
MANF: DODGE SPEC: MMMS F 411 A050

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	100.0	014.7	0.021		00.20	10.00	T NONE	No test data	B	MECH	14.7	72	-297	0.021	0	20

61983 LACING TAPE AIR-TEX 17 GID: ECBSXX
MANF: AIRTEX SPEC: MIL-T-43435

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	023.8	014.5	0.012		00.74	12.00	T SMALL	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	7.31	2.60			No test data		

64466 LACING TAPE AROMATIC POLYAMIDE GID: ECCDXX
MANF: INSULECTRO SPEC: MIL-T-43435B RB0150-042

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.008			04.50	NONE	No test data	No test data							

20593 LACING TAPE BLACK GID: ECCBXX
MANF: BALLY RIBBON MILLS SPEC: ST14P134-02

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3			00.09	12.00	T MOD	No test data	No test data							
X	1	025.9	014.3			00.26	12.00	T MOD									
X	1	030.0	009.0			00.32	12.00	T MOD									

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005784 6

20593 LACING TAPE BLACK (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.2E-6	1.72	.32		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	K 00020.33	

61491 LACING TAPE BRAID NYLON GID: ECCDBS

MANF: GUDEBROD BROS SILK

SPEC: MIL-T-43435T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.006			00.50	NONE
X	1	023.8	014.5	0.006			06.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.2E-6	2.75	.23		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

60439 LACING TAPE DACRON GID: ECCBXX

MANF:

SPEC: MC-8299-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.058			02.30	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.41	.05	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

62851 LACING TAPE F416 TEFLON COATED GID: ECCOXX

MANF: BENTLEY HARRIS

SPEC: MMS-F-416C125

STM-F-416

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	100.0	044.0	0.018		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.021	0	20
B	MECH	14.7	72	-297	0.180	0	20

60522 LACING TAPE FIBERGLAS 50LOF13X GID: ECFVXX

MANF: WESTERN FILAMENT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.025			03.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.44	

61234 LACING TAPE FRL 615-156 PBI GID: ECHECO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.2E-7	6.56	.19		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

60837 LACING TAPE FRL 615-157 PBI GID: ECHECO

MANF: FABRIC RESEARCH LAB

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.2E-7	5.48	.40		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

60836 LACING TAPE FRL 615-158 PBI GID: ECHECO

MANF: FABRIC RESEARCH LAB

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.2E-7	1.64	.38		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005785 8

61136 LACING TAPE FRL 73300-130-5 GID: ECCDCN
MANF: FABRIC RESEARCH LAB

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.8E-6	.83	.09		

ODOR / TOXICITY: No test data

05296 LACING TAPE GLASS/TFE GID: ECGDCN
MANF: BENTLEY HARRIS SPEC: MIL-T-43435BT4
GUDEBROD BROS SILK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.010			01.40	NONE
A	1	030.0	010.0	0.020			00.80	NONE
A	1	030.0	010.0	0.030			01.20	NONE

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY: No test data

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	00007.22	

60470 LACING TAPE GORTEX GID: ECXXXX
MANF: BALLY RIBBON MILLS SPEC: ST14G730
....NO TEST DATA AVAILABLE....

20429 LACING TAPE GORTEX .062 DIA GID: DYCBXX
MANF: BALLY RIBBON MILLS SPEC: ST14G730

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.061			01.70	SMALL
A	1	030.0	009.0	0.045			02.20	SMALL
A	1	033.0	014.3	0.061			02.30	SMALL
C	1	100.0	020.2	0.061		00.35	12.00 T	SMALL

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	9.0E-7	.05	.01		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00027.53	

62539 LACING TAPE GUDE-LACE GID: ECHSXX
MANF: GUDEBROD BROS SILK SPEC: MIL-T-43435T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.010		00.90	07.90	SMALL

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.0E-6	4.68	1.32	1.54	

ODOR / TOXICITY: No test data

61490 LACING TAPE GUDE-SPACE 18DPT-H GID: EUBSXX
MANF: GUDEBROD BROS SILK SPEC: MIL-I-43435

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.58	.06	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00020.77	

63168 LACING TAPE GUDETEMP 718Z NOMEX GID: ECBSXX
MANF: GUDEBROD BROS SILK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.011			04.00	NONE

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	21.48	12.88	19.14	

ODOR / TOXICITY: No test data

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005786 T

60781 LACING TAPE GUDETEMP 723G NOMX GID: ECBSXX
MANF: GUDEBROD BROS SILK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.010			02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	9.55	3.77	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06244 LACING TAPE NEK KEVLAR 49 GID: ECXXXX
MANF: HAWKEYE ENTERPRISES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.015			01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	2.46	.05	1.55	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05609 LACING TAPE NT-15 LOC NOMEX GID: EUBVXX
MANF: BENTLEY HARRIS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.026		00.70	01.70	NONE
C	1	030.0	010.0	0.026		00.70	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.1E-5	4.82	.20		

ODOR

RT	RT WEIGHT	CURE
A	A 00019.84	

TOXICITY

20147 LACING TAPE NT-20 LOC A NOMEX GID: ECBVAK
MANF: BENTLEY HARRIS SPEC: MIL-T-43435
....NO TEST DATA AVAILABLE....

61400 LACING TAPE NT-30 LOC A NOMEX GID: ECBVXX
MANF: BENTLEY HARRIS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5				02.40	NONE
C	2	023.8	014.5	0.019			00.60	NONE
C	1	023.8	014.5	0.019		00.40	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06571 LACING TAPE NT-30 LOC B GREEN GID: ECCAAK
MANF: BENTLEY HARRIS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.025		00.00	00.00	NONE
B	1	020.9	014.7	0.025			08.90	NONE
C	2	020.9	014.7	0.030			00.10	NONE
C	1	020.9	014.7	0.030		00.71	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	K 00020.89	

TOXICITY

00964 LACING TAPE NT-30 LOC B NOMEX GID: ECBVAK
MANF: BENTLEY HARRIS SPEC: MB0135-035 MB0135-035T1
MB0135-035T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.021			02.90	NONE

FSC

RT	FLUID NAME
A	AMMONIA

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0005787 1

Information Handling Services, 2000

00964 LACING TAPE HT-30 LOC B NOMEX (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.018		033	01.30	T NONE
A	1	023.8	014.5	0.385			01.70	NONE
A	1	025.9	014.3	0.300			03.00	NONE
I	1	030.0	010.4			00.19	11.00	T NONE
I	1	033.2	015.5	0.300			06.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-7	3.14	.00		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.33	

06313 LACING TAPE HT-30 LOC B ORANGE GID: ECBVXX

MANF: BENTLEY HARRIS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.9E-6	3.15	.00		16H-347F-0psiaVACUUM

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

60869 LACING TAPE HT-30 NOMEX GID: ECARXX

MANF: BENTLEY HARRIS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.019		00.50	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60866 LACING TAPE HT-30 SPACE 1 INCH GID: ECARXX

MANF: BENTLEY HARRIS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.019		00.03	08.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60855 LACING TAPE HT-30 SPACE.5 INCH GID: ECARXX

MANF: BENTLEY HARRIS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.019		00.03	00:30	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60944 LACING TAPE HT-30-LOC A ORANGE GID: ECBVXX

MANF: BENTLEY HARRIS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.021			00.50	NONE
C	1	023.8	014.5	0.021		00.42	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.10	

61544 LACING TAPE HT-30-TVS NOMEX GID: ECBVAK

MANF: BENTLEY HARRIS SPEC: MB0135-035T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.3	0.020		00.50	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.6E-6	1.81	.10		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

61401 LACING TAPE HT-30-VR GID: ECBVDE

MANF: BENTLEY HARRIS

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005788 3

61401 LACING TAPE NT-30-VR (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.022			06.10	SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.64	.06	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.57	

06517 LACING TAPE NATURAL FIBER/WAX GID: ECXXX

MANF: SPEC: MIL-T-713TN

....NO TEST DATA AVAILABLE....

05987 LACING TAPE NOMEX GID: ECBVXX

MANF: BENTLEY HARRIS SPEC: MB0135-035T1
WESTERN FILAMENT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.015			00.10	NONE
B	1	023.8	014.5	0.015			07.60	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.45	2.08	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 00020.26	

61816 LACING TAPE NOMEX 1251 GID: ECBSXX

MANF: GUDEBROD BROS SILK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.9E-7	4.38	.17		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
No test data		

60860 LACING TAPE NOMEX 1251P GID: ECBVXX

MANF: GUDEBROD BROS SILK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.011		00.39	12.00 T	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.64	.10	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
No test data		

61812 LACING TAPE NOMEX 1251V GID: ECBVDE

MANF: GUDEBROD BROS SILK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.015		00.41	12.00 T	MOD

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.8E-6	2.66	.13		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
No test data		

61664 LACING TAPE NOMEX 1251VC GID: ECBVDE

MANF: GUDEBROD BROS SILK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.016			05.00	NONE
I	1	030.0	010.0	0.019		00.50	12.00 T	SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.13	.14	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005789 5

61815 LACING TAPE NOMEX 1316 GID: ECBSXX
MANF: GUDEBROD BROS SILK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.9E-7	15.53	7.80		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61316 LACING TAPE NOMEX 1317Z GID: ECBVXX
MANF: GUDEBROD BROS SILK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	145.0	0.018			03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	6.2E-7	10.71	4.51		24H-150F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61315 LACING TAPE NOMEX 1318X5 GID: ECBVXX
MANF: GUDEBROD BROS SILK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.018			02.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.2E-7	9.66	4.96		24H-150F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61235 LACING TAPE NOMEX 1342-300 GID: ECBVXX
MANF: GUDEBROD BROS SILK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	3.43	.50		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62324 LACING TAPE NOMEX 1342G GID: ECBVXX
MANF: GUDEBROD BROS SILK SPEC: MB0135-035T2

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00010.41	

TOXICITY

20111 LACING TAPE NOMEX 431 SBR/ML GID: ECXXXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.011			00.10	NONE
C	1	023.8	014.5	0.011		00.74	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20227 LACING TAPE NOMEX 950HOT16 GID: ECBVXX
MANF: WESTERN FILAMENT SPEC: MIL-C-7515
....NO TEST DATA AVAILABLE....

64265 LACING TAPE NOMEX GUDE-TEMP
MANF: GUDEBROD BROS SILK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.78	.04	.00	

ODOR

RT	RT WEIGHT	CURE
	K 00022.29	

TOXICITY

05704 LACING TAPE NOMEX ORANGE GID: ECBVXX
MANF: BENTLEY HARRIS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.80	.02	.00	10H-347F-0psia1E-4/E-6

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005790 1

05704 LACING TAPE NOMEX ORANGE (cont)

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
					10H-347F-0psiaVACUUM			

61396 LACING TAPE NOMEX RD1251X GID: ECBVHD

MANF: GUDEBROD BROS SILK SPEC: MB0135-035

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	2	023.8	014.5	0.019			00.10	NONE	No test data	No test data							
A	1	023.8	014.5	0.019			03.80	NONE									

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	4.6E-6	10.03	3.55			X	00020.29	

06061 LACING TAPE NOMEX/P/N 950H0T16

MANF: WESTERN FILAMENT SPEC: MIL-T-43435T5

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.040			01.30	NONE	No test data	No test data							

62051 LACING TAPE NOMEX/VITON GID: ECBVDE

MANF: BENTLEY HARRIS

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.310		00.00	00.00	NONE	No test data	No test data							

61399 LACING TAPE NOMEX/VITON 1342C GID: ECBVXX

MANF: GUDEBROD BROS SILK

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.018			01.90	NONE	No test data	No test data							
A	1	030.0	009.0	0.018			02.70	NONE									

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.61	.03	.00	1H-350F-		K 00012.97	

60867 LACING TAPE NOMEX/VITON 1342V GID: ECBVDE

MANF: GUDEBROD BROS SILK SPEC: MB0135-035 MB0135-035T1

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.014			03.60	SMALL	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	3.73	.09	.00	1H-302F-	A	A 00020.01	
					3H-68F-			

60633 LACING TAPE NOMEX/VITON 1342VC GID: ECBVDE

MANF: GUDEBROD BROS SILK SPEC: MB0135-035T1

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	023.8	014.5	0.018			06.50	SMALL	No test data	No test data							
X	1	025.9	014.3	0.020		00.40	12.00	T MOD									
I	1	025.9	014.3	0.018		00.34	12.00	T NONE									
X	1	030.0	009.0	0.020		00.40	12.00	T MOD									

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	2.3E-6	1.79	.04	1.45	60H-350F-		A 00020.98	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005791 3

05505 LACING TAPE NYLON GID: ECBSXX
MANF: GUDEBROD BROS SILK SPEC: MIL-T-43435BT1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.011		00.50	12.00	T MOD
X	1	030.0	010.0	0.011		01.60	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.16	.03	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

60504 LACING TAPE NYLON GID: ECBSXX
MANF: SPEC: MIL-T-713
....NO TEST DATA AVAILABLE....

63169 LACING TAPE NYLON GID: ECBSXX
MANF: SPEC: MS3368-1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.3	0.075		00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.88	.02	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

20189 LACING TAPE NYLON 17X POLYAMID GID: ECBSXX
MANF: EON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.011			06.10	SMALL
C	1	023.8	014.5	0.011		00.97	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.0E-6	3.97	1.17		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
V	00016.80	

69848 LACING TAPE NYLON BRAID GID: ECBSXX
MANF: BENDIX
....NO TEST DATA AVAILABLE....

20119 LACING TAPE NYLON/DACRON LC136 GID: ECBSXX
MANF: ALPHA WIRE CORP SPEC: MIL-T-43435T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.013		00.00	00.00	NONE
B	1	023.8	014.5	0.013			06.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.37	3.39	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.27	

20271 LACING TAPE NYLON/RUBBER 18H GID: ECBSHD
MANF: GUDEBROD BROS SILK SPEC: MIL-T-43435T1/C

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.012		00.27	12.00	T MOD
X	1	023.8	014.5	0.012		00.69	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
V	00010.03	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005792 5

60482 LACING TAPE PBI/VITON 1330 GID: ECHEXX

MANF: GUDEBROD BROS SILK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.011			02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	9.08	.02	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61548 LACING TAPE PBI/VITON 1330V GID: ECHEDE

MANF: GUDEBROD BROS SILK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.016			02.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.8E-6	6.96	.06		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60861 LACING TAPE PBI/VITON 1330VC GID: ECHEDE

MANF: GUDEBROD BROS SILK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.015			02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.98	.06	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20152 LACING TAPE POLYESTER GID: DYCBIA

MANF: GENERAL ELECTRIC

SPEC: MIL-T-43435

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.007		00.10	12.10	T NONE
X	1	023.8	014.5	0.007		01.29	12.10	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.23	.44	.00	

ODOR

RT	RT WEIGHT	CURE
A	K 00010.92	

TOXICITY

20336 LACING TAPE POLYESTER 2298 GID: ECCBXX

MANF: BALLY RIBBON MILLS

SPEC: ST14P134 ST14P134-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.080		00.18	12.00	T MOD
X	1	023.8	014.5	0.080		00.33	12.00	T MOD
X	2	025.9	014.3	0.072		00.16	12.00	T MOD
X	1	025.9	014.3	0.072		00.31	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.1E-7	.35	.10		

ODOR

RT	RT WEIGHT	CURE
A	V 00020.47	

TOXICITY

20124 LACING TAPE POLYESTER AIR-TEX 217 GID: ECCBAF

MANF: EON CORP

SPEC: MIL-T-43435T2E

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.011		00.18	12.00	T SMALL
C	1	023.8	014.5	0.011		01.93	07.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.2E-6	2.98	.12		

ODOR

RT	RT WEIGHT	CURE
A	V 00020.65	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005793 7

20592 LACING TAPE POLYESTER RED GID: ECCBXX

MANF: BALLY RIBBON MILLS SPEC: ST14P134-03

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3			00.06	12.00	T MOD
X	1	025.9	014.3			00.31	12.00	T MOD
X	1	030.0	009.0			00.41	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	1.10	.05		

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.27	

TOXICITY

63170 LACING TAPE POLYESTER/DACRON GID: ECCBXX

MANF: GUDEBROD BROS SILK SPEC: MIL-T-43435

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.3	0.011		00.57	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62885 LACING TAPE PTFE ENAMELED GID: ECCOXX

MANF: BENTLEY HARRIS SPEC: MMS-F-416 MMS-F-4160125
MMS-F-416C125

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.016	0	20

64892 LACING TAPE PTFE/GLASS GID: ECCNFV

MANF: DODGE
OAK INDUSTRIES SPEC: MMS-F-417 STM-F-416
STM-F-4177

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.022	0	20

60937 LACING TAPE PYROLACE NT 30LOCC GID: ECBVAK

MANF: BENTLEY HARRIS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.019		00.37	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.7E-6	1.46	.08		

ODOR

RT	RT	WEIGHT	CURE
A	A	00010.02	

TOXICITY

01978 LACING TAPE PYROLACE STFE-40B GID: ECCNIA

MANF: BENTLEY HARRIS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.016			01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.04	.00	.00	

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.76	

TOXICITY

62281 LACING TAPE SCOTCH GID: ECXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.003	0.003		00.10	NONE
B	1	025.9	014.3	0.003	0.003		08.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00020.57	

TOXICITY

MSFC-HDBK-527 REV F 9999942 0005794 9

Information Handling Services, 2000

85373 LACING TAPE STFE-30B GID: ECCNIA
MANF: BENTLEY HARRIS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	38.8	

85375 LACING TAPE STFE-80B GID: ECXXXX
MANF: BENTLEY HARRIS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	39.4	

05979 LACING TAPE STUR-30 GID: ECDEIA
MANF: BENTLEY HARRIS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.013		00.05	01.38	NONE
A	1	023.8	014.5	0.016			00.70	NONE
A	1	025.9	014.3	0.013		00.08	01.75	NONE
A	1	030.0	09.00	0.013		00.03	01.25	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.2E-7	.03	.02		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

61442 LACING TAPE STUR-D-LACE 18DR-E
....NO TEST DATA AVAILABLE....

65258 LACING TAPE T3333 GID: ECXXXX
MANF: WARREN WIRE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.020		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05914 LACING TAPE TEMP-LACE H/276H GID: ECCNXX
MANF: GUDEBROD BROS SILK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.012			01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.3E-6	.32	.01		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05925 LACING TAPE TFE 2560 GID: ECCNXX
MANF: GUDEBROD BROS SILK SPEC: MIL-T-43435T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.005			03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00003.00	

05900 LACING TAPE TFE/RUBBER H 231H GID: ECCNHD
MANF: GUDEBROD BROS SILK SPEC: MIL-T-43435CT3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.011			02.30	NONE
A	1	025.9	014.3	0.011		00.18	05.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0005795 0

Information Handling Services, 2000

05900 LACING TAPE TFE/RUBBER H 231H (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.94	.25	.60	

ODOR

RT	RT WEIGHT	CURE
V	12.3	

TOXICITY

20703 LACING TAPE TG-30 20AWG GID: EDCOIA

MANF: BENTLEY HARRIS SPEC: STSV107-3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	4	025.9	014.3	0.032			00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	025.9	014.3	0.032	12.00	00.00

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.47	.20		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.04	

TOXICITY

05628 LACING TAPE THERMOFLEX 1200 GID: ECXXXX

....NO TEST DATA AVAILABLE....

20255 LACQUER ACRYLIC GID: ASAKXX

MANF: SPEC: MIL-L-81352

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.71	.02	7.33	168H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20786 LACQUER ACRYLIC NITROCEL 17038 GID: AKXXXX

MANF: AQM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.001	0.003	00.00	00.00	NONE
A	1	020.9	014.7	0.001	0.003		01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.66	.03	.31	10H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20787 LACQUER CELLULOSE NITRATE BLAK GID: ASXXXX

MANF: AQM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.001	0.003	00.00	00.00	NONE
C	1	020.9	014.7	0.001	0.003	01.54	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	12.39	3.82	.34	24H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20785 LACQUER CELLULOSE NITRATE YELLOW GID: AKAYXX

MANF: AQM SPEC: TT-L-32

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.001	0.003	00.00	00.00	NONE
B	1	020.9	014.7	0.001	0.003		06.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.4E-6	10.50	1.80	.20	10H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005796 2

20204 LACQUER GREEN COLOR 11105 GID: ASXXXX

SPEC: FED STD 595

MANF: AQM

....NO TEST DATA AVAILABLE....

20790 LACQUER VHT 1200F SP102 17038 GID: ASXXXX

MANF: SPEREX CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003	00.00	00.00	NONE
A	1	025.9	014.3	0.001	0.003		01.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-6	1.40	.85	.05	24H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20789 LACQUER VHT1200F SP101 17875 GID: ASXXXX

MANF: SPEREX CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		00.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-6	1.02	.54	.08	24H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20043 LACQUER YELLOW

MANF: AQM

....NO TEST DATA AVAILABLE....

80090 LAMIN 3 PLY ALUMINUM FOIL GID: COFKXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.011		00.50	08.90	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	K 22.230	

TOXICITY

61952 LAMIN ACRYLACON/FIBERGLASS RHF GID: COEMFV

MANF: DART INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.240			01.20	NONE
A	1	033.0	014.3	0.243			01.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	X 00070.94	

TOXICITY

60689 LAMIN ASBESTOS/FIBERGLASS RVV647F GID: CRFLXX

MANF: RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.100		00.00	00.00	NONE
A	1	043.2	008.0	0.100		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	X 00120.06	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005797 4

60296 LAMIN BALSA WOOD/ALUMINUM FACING
MANF: SPEC: MIL-S-17917

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.25	.07	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62431 LAMIN CARBON/CARBON REINFORCED GID: COFOXX
MANF: LTV AEROSPACE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.6E-6	.01	.01		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62070 LAMIN CARBON/PHENOLIC 2267-01 GID: COFOBX
MANF: HAVEG

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-7	3.66	.02		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62105 LAMIN CARBON/PHENOLIC 2269-01 GID: COFOBX
MANF: HAVEG SPEC: 2269-01 FM5055M

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-7	2.05	.02		216H-300F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62046 LAMIN CE9020/120/45% RC GID: CRBGXX
MANF: FERRO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.014		00.49	11.90	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60990 LAMIN CLEER-ADHERE 65001 GID: COXXXX
MANF: C-LINE PRODUCTS INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00020.13	

TOXICITY

61073 LAMIN CMC608-2 POLYIMIDE WITH COPPER GID: COCDMC
MANF: OAK INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.006			01.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.8E-7	.23	.08		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61725 LAMIN CORLAR 4102/KEVLAR 49-181 GID: COCBXX
MANF: GENERAL DYNAMICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	X 00020.11	2H-250F-0psiaVACUUM

TOXICITY

61720 LAMIN CORLAR 5105/KEVLAR 49-181 GID: COBGCD
MANF: GENERAL DYNAMICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	B 00020.72	3H-350F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005798 6

61702 LAMIN CORLAR 5134/KEVLAR 49-181 GID: COBGXX

MANF: GENERAL DYNAMICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.040			02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	V	00020.13	2H-250F-

TOXICITY

61722 LAMIN CORLAR 6101-2/KEVLAR 49-18 GID: COBXXX

MANF: GENERAL DYNAMICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.2E-6	1.14	.01		SEE TEST REPORT

ODOR

RT	RT	WEIGHT	CURE
A	X	00020.09	SEE TEST REPORT

TOXICITY

61721 LAMIN CORLAR 6113/KEVLAR 49-181 GID: COBXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.2E-6	1.23	.00		

ODOR

RT	RT	WEIGHT	CURE
A	V	00020.23	

TOXICITY

01728 LAMIN COTTON/PHENOLIC GID: COBXXX

SPEC: MIL-H-83282FBG MIL-P-15035FBE

MANF: SYNTHANE-TAYLOR CORP
WESTINGHOUSE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.063			01.80	NONE
C	1	030.0	010.0	0.063		0.10	12.00	T NONE

FSC

RT	FLUID NAME
C	HYD

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.19	.01	.00	8H-212F-

ODOR

RT	RT	WEIGHT	CURE
	X	22.519	

TOXICITY

65112 LAMIN CYCOM 6101-2/7781 GID: COXXXX

MANF: AMERICAN CYANAMID

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.73	.57	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

63154 LAMIN DC6-1104 AND REFSET COATED GID: COXXXX

MANF: YDE BOARD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.065			01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60801 LAMIN DECLAD 810 COPPER COATING GID: COCNXX

MANF: KEENE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.2E-6	.04	.01	.02	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05452 LAMIN DUCT 02GY3 TC URETHANE 17875 GID: FCBGJH

SPEC: MB0130-127 MIL-C-83286

MANF: DEFT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	025.9	014.3				00.20	NONE
A	1	025.9	014.3				01.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005799 8

64186 LAMIN DUROID BOARD 6006 GID: COXXXX
MANF: ROGERS CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00005.87	

TOXICITY

64194 LAMIN DUROID BOARD 6010 GID: COXXXX
MANF: ROGERS CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00006.14	

TOXICITY

61718 LAMIN EDGE LIGHT PANEL EPOXY/GLASS/ACRYLIC/VINYL GID: COAEAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	X 00012.13	

TOXICITY

62145 LAMIN EPOCAST 31/9216/1581 CLOTH GID: COBGIA
MANF: FURANE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.74	.02		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61813 LAMIN EPOXY AP3012A GID: COBGXX
MANF: ARROWHEAD PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.060		00.16	07.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65213 LAMIN EPOXY CL522 GID: COBGXX
MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.6E-6	.64	.22	.02	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20279 LAMIN EPOXY MG2 NOVOLAC/PHENOL GID: COBGBX
....NO TEST DATA AVAILABLE....

05820 LAMIN EPOXY/ARAMID GID: COBGBV
MANF: FERRO
HEXCEL
SPEC: MB0130-127T8

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.020			03.20	NONE
X	1	030.0	009.0	0.019		00.33	12.10	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.6E-6	2.17	.00	1.47	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20796 LAMIN EPOXY/ARAMID F164 GID: COBGJH
MANF: FERRO
HEXCEL
SPEC: MB0130-127T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.022			02.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.6E-6	1.53	.00		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.43	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005800 0

05076 LAMIN EPOXY/BORON SP296 GID: CPBGME

MANF: 3M CO

SPEC: MB0130-101T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.082		00.00	00.00	NONE
C	1	023.8	014.5	0.082		00.10	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.25	.01	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.05	

61443 LAMIN EPOXY/BORON/TITANIUM SHEET GID: COBGME

MANF: HAMILTON STANDARD

SPEC: ST0130LB0007

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.043			01.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20634 LAMIN EPOXY/CAB-O-SIL GID: COBGXX

MANF: HAMILTON STANDARD

SPEC: SVHS 8090T15

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.094	0.125		00.40	MOD
X	1	033.0	014.3	0.105	0.125		05.50	MOD
X	2	100.0	020.2	0.127	0.125	00.14	12.00 T	MOD
X	1	100.0	020.2	0.127	0.125	00.27	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.9E-6	1.04	.02		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.02	

02955 LAMIN EPOXY/GLASS GID: COBGIA

MANF: AIN PLASTICS
WESTINGHOUSE

SPEC: MC8257-01
MIL-P-18177GEB

MIL-P-18177
MIL-P-18177GEBG11

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.125			00.70	NONE
A	1	020.9	014.7	0.066			01.90	SMALL
A	1	020.9	014.7	0.062			01.60	SMALL
A	1	024.5	014.5	0.240			00.25	NONE
X	2	025.9	014.3	0.014			01.20	MOD
X	1	025.9	014.3	0.014		00.41	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.2E-6	.53	.00	.23	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00022.58	

05137 LAMIN EPOXY/GLASS GID: COGDBG

MANF: HEXCEL
LTV AEROSPACE CORP
U S POLYMERIC

SPEC: MB0130-105T3C1

MB0130-105T8GP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.246		00.01	00.20	SMALL
X	1	023.8	014.5	0.050			04.90	MOD
A	1	023.8	014.5	0.074			00.90	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05223 LAMIN EPOXY/GLASS GID: COBGIA

MANF: SYNTHANE-TAYLOR CORP

SPEC: MIL-P-13949GEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.8	014.3	0.068		00.15	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

05335 LAMIN EPOXY/GLASS GID: CRAGIA
MANF: NELCO PRODUCTS SPEC: MIL-G-55636

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.010			00.30	NONE
C	1	023.8	014.5	0.010		00.71	12.00	T NONE
C	2	025.8	014.3	0.009			00.30	NONE
C	1	025.8	014.3	0.009		01.03	12.00	T NONE
X	1	030.0	009.0	0.009		00.70	12.00	T MOD

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY: No test data

ODOR: A

TOXICITY: A 00019.83

05655 LAMIN EPOXY/GLASS GID: COBGIA
MANF: CIRCUIT INDUSTRIES SPEC: MIL-P-13949/4 MIL-P-13949GFN
SYNTHANE-TAYLOR CORP MIL-P-18177C

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.098			00.10	NONE
A	1	023.8	014.5	0.098			02.50	SMALL
A	1	024.5	014.3	0.097			01.60	SMALL
A	1	024.5	014.3	0.063			02.90	SMALL
B	1	030.0	014.3	0.098			08.20	SMALL
X	1	033.2	015.5	0.097		00.06	12.00	T MOD

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.1E-7	.20	.00		

ODOR: A

TOXICITY: A 00020.10

06309 LAMIN EPOXY/GLASS GID: COBGIA
MANF: DORCO ELECTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3				01.20	MOD

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.04	.23	.00	2H-120F-

ODOR: No test data

TOXICITY

20312 LAMIN EPOXY/GLASS GID: BBBGFV
MANF: A & M ENGINEERING SPEC: MIL-P-25421BT2. SVHS 798T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.165			00.10	NONE
X	1	025.9	014.3	0.165		00.05	12.00	T MOD

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.28	.01	.00	

ODOR: RT

TOXICITY: A 00009.70

61530 LAMIN EPOXY/GLASS GID: COBGIA
MANF: A & M ENGINEERING SPEC: MIL-C-9084C2 MIL-C-9084CT8A
MIL-P-25421BT2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.032		00.28	12.00	T MOD
A	1	024.5	014.5	0.370			00.10	NONE

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY: No test data

ODOR: RT

TOXICITY: K 00027.50

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005802 4

61752 LAMIN EPOXY/GLASS GID: CRBGFV
MANF: NARMCO
U S POLYMERIC
SPEC: MB0130-105

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.063			00.10	NONE
B	1	023.8	014.5	0.063			06.10	SMALL
B	2	023.8	014.5	0.060			00.10	NONE
B	1	023.8	014.5	0.060			09.90	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
A	K	00020.07	

62477 LAMIN EPOXY/GLASS GID: EZBGFV
MANF: KOLLMORGEN CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.087			00.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.61	.01	.00	

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	A	00020.06	

63161 LAMIN EPOXY/GLASS GID: COBGIA
MANF: U O PRODUCTS
SPEC: MIL-P-13949GFN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.063		00.00	00.00	NONE
A	1	020.9	014.7	0.063			04.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.29	.01	.00	

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
No test data			

63157 LAMIN EPOXY/GLASS 185206 GID: COBGGD
MANF: RCA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	0.062		00.55	03.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06018 LAMIN EPOXY/GLASS 500 GID: COBGIA
MANF: SYNTHANE-TAYLOR CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.010			00.20	NONE
X	1	023.8	014.5	0.010		00.43	10.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
A	V	00027.30	

61412 LAMIN EPOXY/GLASS 7070664 GID: COBGIA
MANF: WESTINGHOUSE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	009.0	0.061		00.17	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.43	.02	.00	

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
No test data			

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005803 6

20532 LAMIN EPOXY/GLASS 7781/550/P650M GID: CRCDXX

MANF: U S POLYMERIC SPEC: HS 798T32

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.079			00.20	NONE
A	1	025.9	014.3	0.078			01.00	NONE
A	1	033.0	014.3	0.074			02.40	NONE
I	1	100.0	019.0	0.076		00.14	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.69	.01		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00020.63	

61995 LAMIN EPOXY/GLASS AEROLAM 110 GID: CRFVBG

MANF: MCDONNELL DOUGLAS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.449			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05407 LAMIN EPOXY/GLASS AEROLAM 110/RP57 GID: COIAXX

MANF: REN PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.430		00.00	00.00	NONE
B	1	023.8	014.5	0.430		00.01	07.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.3E-6	1.65	.01		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

63172 LAMIN EPOXY/GLASS AUGAT 8136URGI GID: COBGIA

MANF: AUGAT INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.562			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61482 LAMIN EPOXY/GLASS B10-108-63 GID: COBGIA

MANF: FORTIN CORP SPEC: MIL-G-55636

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.004		01.67	12.00	T NONE
I	1	030.0	008.0	0.004		01.56	12.00	T NONE
I	1	040.0	008.0	0.004		03.01	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.6E-6	.74	.30		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00008.40	

62313 LAMIN EPOXY/GLASS CE3201 GID: COHMBG

MANF: FERRO SPEC: HMS 20-1590

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	1.000		00.04	10.40	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05406 LAMIN EPOXY/GLASS CE9000 GID: COIABG

MANF: FERRO SPEC: TB0130-302

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.108			00.10	NONE
C	1	023.8	014.5	0.108		00.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005804 8

05406 LAMIN EPOXY/GLASS CE9000 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	023.8				00.06	18.50	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	.57	.01		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61763 LAMIN EPOXY/GLASS CE9010 GID: COBGIA

MANF: FERRO SPEC: MB0130-105C1GFR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.020			07.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05414 LAMIN EPOXY/GLASS CE9010/120 GID: CRBGXX

MANF: FERRO SPEC: MB0130-105T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.009			00.10	NONE
A	1	023.8	014.5	0.009			04.00	NONE
A	1	023.8	014.5	0.011			02.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.4E-6	1.29	.01		1H-70F-
					1H-350F-

ODOR

RT	RT WEIGHT	CURE
A	B 00020.10	1H-70F-12.4psia
		1H-350F-

TOXICITY

61077 LAMIN EPOXY/GLASS CE9010/181 KEVLAR 49 GID: CKBGJH

MANF: FERRO SPEC: MB0130-127T3

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.7E-6	1.61	.00		

ODOR

RT	RT WEIGHT	CURE
A	Y 00020.14	

TOXICITY

80980 LAMIN EPOXY/GLASS CE9010/7781 TOX RATE STUDY

MANF: FERRO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	K 00019.85	

TOXICITY

64041 LAMIN EPOXY/GLASS CE9010A/120 GID: CRBGXX

MANF: FERRO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.036	01	09

64288 LAMIN EPOXY/GLASS CE9010A/7781 GID: COBGXX

MANF: ARC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.7				02.13	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60740 LAMIN EPOXY/GLASS CE9020/7781 GID: CRBGXX

MANF: FERRO SPEC: MB0130-105T8BC1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.210			01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005805 T

62047 LAMIN EPOXY/GLASS CE9020/KEVLAR 49 GID: COJHBG

MANF: FERRO SPEC: MB0130-127T3

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
I	1	023.8	014.5	0.017		00.44	11.90	T NONE	No test data		No test data						

63280 LAMIN EPOXY/GLASS CIRCUIT BOARD GID: CKBGXX

MANF: JAPAN AVIONICS CO SPEC: NASDA-QTS-1023
NIPPON AVIOTRONICS

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.5	0.062			00.50	NONE	No test data		No test data						
I	1	024.5	014.5	0.060			01.00	NONE									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	67.237	

05783 LAMIN EPOXY/GLASS COATED WITH CE1155 GID: COBGCQ

MANF: CONAP SPEC: MIL-P-18177GEE
NELCO PRODUCTS

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
B	1	023.8	014.5	0.067		00.09	07.30	NONE	No test data		No test data						

06176 LAMIN EPOXY/GLASS CORDOPREG E293 GID: COBGIA

MANF: FERRO SPEC: G E 47A101715P1 ST94G086-01

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.056			00.20	NONE	No test data		No test data						
X	1	025.9	014.3	0.056		00.13	12.00	T MOD									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	4.2E-7	.17	.00			A	A	00020.38	

61347 LAMIN EPOXY/GLASS DX501/7581/181 GID: COBGXX

MANF: DUPONT

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.026			02.60	SMALL	No test data		No test data						

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	3.6E-6	.38	.00			A	K	00074.95	

62010 LAMIN EPOXY/GLASS E720 GID: COBGIA

MANF: STEVENS MOLDED PROD SPEC: MIL-C-9084 MIL-R-9300

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
C	2	029.1	014.7	0.030		00.02	00.10	SMALL	No test data		No test data						
C	1	029.1	014.7	0.030		00.17	12.00	T SMALL									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	1.0E-6	.54	.04	.00		No test data			

61777 LAMIN EPOXY/GLASS E720E/7581 FR GID: COBGIA

MANF: U S POLYMERIC SPEC: MB0130-105T8BC1

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
C	2	023.8	014.5	0.009			00.10	NONE	No test data		No test data						

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005806 1

61777 LAMIN EPOXY/GLASS E720E/7581 FR (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	023.8	014.5	0.009		00.50	11.70 T	NONE
C	1	023.8	014.5	0.054		00.09	11.70 T	NONE
A	1	023.8	014.5	0.102			00.50	NONE
B	2	023.8	014.5	0.020			00.10	NONE
B	1	023.8	014.5	0.020		00.24	09.50	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.0E-6	.26	.01		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.35	

TOXICITY

60443 LAMIN EPOXY/GLASS E747/VOLAN/1581 GID: COBGIA

MANF: U S POLYMERIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.2E-7	.17	.01	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

06194 LAMIN EPOXY/GLASS E760A/7581/D6090 GID: COBGIA

MANF: BEECH AIRCRAFT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.155			01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-7	.33	.00		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05684 LAMIN EPOXY/GLASS EG752 GID: COBGIA

MANF: SPEC: AB0130-043

....NO TEST DATA AVAILABLE....

20549 LAMIN EPOXY/GLASS EPON APCO 434/SONITE 41 GID: CRBGXX

MANF: SHELL CHEMICAL SPEC: SVHS 8091T10
SMOOTH-ON INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.140		00.10	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.43	.00		

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.37	

TOXICITY

61435 LAMIN EPOXY/GLASS F164 GID: COBGIA

MANF: HEXCEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.035			02.10	NONE
A	1	023.8	014.5	0.064			00.90	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61436 LAMIN EPOXY/GLASS F164-1 GID: COBGIA

MANF: HEXCEL SPEC: MB0130-105T8BC1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.070			01.20	SMALL
A	1	023.8	014.5	0.060			01.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61106 LAMIN EPOXY/GLASS F164-1/7781 GID: COBGIA

MANF: HEXCEL SPEC: MB0130-105 MB0130-105T8C1

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005807 3

61106 LAMIN EPOXY/GLASS F164-1/7781 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
I	1	023.8	014.5	0.017		00.32	12.00	T	SMALL
I	1	023.8	014.5	0.036		00.14	12.00	T	SMALL
A	1	023.8	014.5	0.087			01.40		SMALL
A	1	023.8	014.5	0.049		00.07	03.00		SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61432 LAMIN EPOXY/GLASS F164/7781 GID: COBGIA

MANF: HEXCEL

SPEC: MB0130-105 MB0130-105T3B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
C	2	023.8	014.5	0.056			00.10		NONE
C	1	023.8	014.5	0.056		00.08	12.00	T	SMALL
A	1	023.8	014.5	0.074			01.30		NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05056 LAMIN EPOXY/GLASS FB400 GF GID: COBGIA

MANF: SYNTHANE-TAYLOR CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
I	1	030.0	009.0	0.062		00.14	12.10	T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63486 LAMIN EPOXY/GLASS FB600 GID: COBGIA

MANF: SYNTHANE-TAYLOR CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
C	2	025.9	014.3	0.012		00.02	00.20		NONE
C	1	025.9	014.3	0.012		00.50	12.00	T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.2E-6	.49	.03	.15	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00021.88	

60083 LAMIN EPOXY/GLASS FF91

MANF: AEROFAB

SPEC: MIL-P-18177

....NO TEST DATA AVAILABLE....

63155 LAMIN EPOXY/GLASS FIBER GID: COBGGD

MANF: MULTIWIRE

SPEC: MIL-P-13949

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	024.5	014.5	0.115			00.70		NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61426 LAMIN EPOXY/GLASS FR TYPE GF GID: COBGIA

MANF: SYNTHANE-TAYLOR CORP

SPEC: MIL-P-13949

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	025.9	014.3	0.064			01.10		SMALL
A	1	030.0	014.3	0.063			00.80		SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05543 LAMIN EPOXY/GLASS FR4 GID: COBGIA

MANF: INSULECTRO

SPEC: MC8024-1 MIL-P-18177

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	020.9	014.7	0.055			01.50		NONE
C	2	023.8	014.5	0.032			00.10		NONE
C	1	023.8	014.5	0.032		00.2	12.00	T	NONE
B	1	025.9	014.3	0.055		00.12	07.00		NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005808 5

05543 LAMIN EPOXY/GLASS FR4 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.32	.02	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05812 LAMIN EPOXY/GLASS FURANE 203 GID: COGEX

MANF: FURANE

....NO TEST DATA AVAILABLE....

20139 LAMIN EPOXY/GLASS G10 GID: COBGXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.49	.01	.00	

ODOR

RT	RT WEIGHT	CURE
K	37.4	

TOXICITY

62375 LAMIN EPOXY/GLASS G10FR/SR240 GID: COBGIA

MANF: GENERAL ELECTRIC
NORPLEX OAK INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.063			00.10	MOD
X	1	025.9	014.3	0.063		00.06	09.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.43	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61425 LAMIN EPOXY/GLASS GENERAL PURPOSE GID: COBGIA

MANF: SYNTHANE-TAYLOR CORP SPEC: MIL-P-13949/3
TECHNICAL CIRCUITS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.063			02.40	SMALL
A	1	025.9	014.3	0.061			00.30	NONE
A	1	030.0	010.0	0.090		00.09	03.87	SMALL
A	1	033.0	014.3	0.061			00.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.27	1.44	.00	

ODOR

RT	RT WEIGHT	CURE
A	V 00020.07	

TOXICITY

05717 LAMIN EPOXY/GLASS K1041 POLYURETHANE COATED GID: DTCKCQ

MANF: MIDWEST PAINT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.0E-6	.10	.02		12H-200F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

02945 LAMIN EPOXY/GLASS L-P-509 TYPE G10 GID: COBGIA

MANF: SYNTHANE-TAYLOR CORP SPEC: MIL-P-18177GEE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.094			00.90	NONE
I	1	023.8	014.5	0.036		00.10	12.00	T NONE
C	2	023.8	014.5	0.034			00.30	NONE
C	1	023.8	014.5	0.034		00.16	12.00	T SMALL
A	1	023.8	014.5	0.096			03.70	NONE
I	1	025.8	014.3	0.070		00.12	12.00	T NONE
X	1	025.9	014.3	0.118		00.06	11.90	T MOD
I	1	030.0	009.0	0.062		00.13	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.6E-6	.26	.00		

ODOR

RT	RT WEIGHT	CURE
A	00130.54	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005809 7

05882 LAMIN EPOXY/GLASS MIB MATERIAL GID: COBGIA

....NO TEST DATA AVAILABLE....

61475 LAMIN EPOXY/GLASS N4105 GID: COBGIA

MANF: NELCO PRODUCTS

SPEC: MIL-P-18177GEE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.022			00.20	NONE
C	1	023.8	014.5	0.022		00.33	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.94	.17	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62274 LAMIN EPOXY/GLASS NEMA G11 GID: COBGIA

MANF: WESTINGHOUSE

SPEC: H23842

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.4	0.063		00.04	11.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.250	01	01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.63	.02	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63176 LAMIN EPOXY/GLASS OH AUGAT UL1 GID: COGDBG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.062			00.25	NONE
A	1	024.5	014.5	0.014			06.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61979 LAMIN EPOXY/GLASS PC BOARD GID: COBGIA

MANF: TEKTRONIX

SPEC: RA 3265-02
RB 3835-01

RA 4747-00
RF 3884-00

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.068		00.07	03.90	T SMALL
I	1	025.9	014.3	0.062		00.12	10.40	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63898 LAMIN EPOXY/GLASS PC BOARD GID: COXXXX

MANF: NIPPON AVIOTRONICS

SPEC: NASD-QTS-1023

NASDA-QTS-1023

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
X	00362.10	

TOXICITY

06367 LAMIN EPOXY/GLASS RADP70057 GID: CRBGXX

....NO TEST DATA AVAILABLE....

20707 LAMIN EPOXY/GLASS RP4002A GID: CRXXXX

MANF: AIR-LOCK INC

SPEC: LAYUP A/L 23524

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.063		00.26	12.00	T SMALL

FSC

RT	FLUID NAME
A	AMMONIA

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	K 00020.10	

TOXICITY

64286 LAMIN EPOXY/GLASS S901 GID: COXXXX

MANF: BASD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.8E-6	.16	.00	.08	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005810 3

64446 LAMIN EPOXY/GLASS STRIPPED GID: COBGIA
MANF: HONEYWELL SPEC: MC8025-01

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.060			00.90	NONE	No test data		No test data							

65396 LAMIN EPOXY/GLASS STRUCOL R1602 GID: COXXXX
MANF: DEFT

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.58	.01	.00	1H-356F-	No test data		

20633 LAMIN EPOXY/GLASS SVHS 8091T11 GID: COBGIA
MANF: HAMILTON STANDARD

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	025.9	014.3	0.131			01.30	NONE	No test data		No test data							
C	1	025.9	014.3	0.131		00.13	11.90	T SMALL										

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	6.9E-6	.91	.03			A	K 00019.78	

20632 LAMIN EPOXY/GLASS SVHS 8091T13 GID: COBGIA
MANF: HAMILTON STANDARD

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	025.9	014.3			00.03	12.00	T NONE	No test data		No test data							
C	1	025.9	014.3			00.49	12.00	T SMALL										

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
I	6.9E-6	1.39	.40			A	K 00020.01	

20444 LAMIN EPOXY/GLASS SVHS 8091T2 GID: COBGIA
MANF: HAMILTON STANDARD

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.149			01.40	MOD	No test data		No test data							
X	1	025.9	014.3	0.149		00.06	12.00	T MOD										

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	6.3E-7	2.64	.17			A	V 00019.97	

20445 LAMIN EPOXY/GLASS SVHS 8091T3 GID: COBGIA
MANF: HAMILTON STANDARD

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.037		00.15	10.80	T MOD	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	6.3E-7	1.03	.01				X 00024.96	

20446 LAMIN EPOXY/GLASS SVHS 8091T4 GID: COBGIA
MANF: HAMILTON STANDARD

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.115			08.70	MOD	No test data		No test data							
X	1	025.9	014.3	0.115		00.08	12.00	T NONE										

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005811 5

20446 LAMIN EPOXY/GLASS SVHS 8091T4 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.3E-7	.37	.00		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.04	

TOXICITY

61514 LAMIN EPOXY/GLASS TAYLORCLAD FIREBAN GID: COBGIA

MANF: SYNTHANE-TAYLOR CORP

SPEC: MIL-P-13949E

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.094			01.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.64	.03	.00	

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.06	

TOXICITY

61489 LAMIN EPOXY/GLASS TYPE GF GID: COBGIA

MANF: FORTIN CORP

SPEC: MIL-P-55617TLGF

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.008			01.90	SMALL
A	1	030.0	009.0	0.008			00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.20	.00	.00	

ODOR

RT	RT	WEIGHT	CURE
A	A	00047.71	

TOXICITY

05337 LAMIN EPOXY/GLASS URALANE 5750/FC721 GID: COIAXX

....NO TEST DATA AVAILABLE....

63397 LAMIN EPOXY/GLASS VIBRATION DAMPER

MANF: GENERAL ELECTRIC

SPEC: MIL-P-13949E

STM-K-776

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.412			00.50	NONE
X	1	020.9	014.7	0.412		00.05	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62433 LAMIN EPOXY/GLASS WITH EPOXYLITE 9653 GID: BDBGIA

MANF: EPOXYLITE CORP
GENERAL ELECTRIC

SPEC: MIL-P-13949TYGF

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.058		00.10	07.00	T NONE
I	1	023.8	014.5	0.059		00.08	07.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63398 LAMIN EPOXY/GLASS WITH NRH GID: COBGIA

MANF: HEXCEL

SPEC: MIL-C-81986

MIL-P-18177

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.3	0.562		00.04	08.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61143 LAMIN EPOXY/GLASS XYLOK 210 GID: CRBGIA

MANF: CIBA-GEIGY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.030			01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.6E-6	.31	.00		24H-250F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00080.15	24H-250F-

TOXICITY

MSFC-HDBK-527 REV F 9999942 0005812 7

Information Handling Services, 2000

05761 LAMIN EPOXY/GLASS/1B31 POLYURETHANE COATED GID: COBGXX

....NO TEST DATA AVAILABLE....

63173 LAMIN EPOXY/GLASS/COPPER G10 GID: COBGGD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	024.5	014.5	0.060			06.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05166 LAMIN EPOXY/GLASS/DC3140 COATED GID: COBGCK

MANF: HYDRO AIRE
NORPLEX OAK INDUSTRIES

SPEC: AB0130-125
MIL-P-13949

MIL-G-53636

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.080			00.10	NONE
X	1	023.8	014.5	0.080			01.00	MOD
A	1	030.0	009.0	0.085			02.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00169.72	

05273 LAMIN EPOXY/GLASS/PHENOLIC ME449-0141 GID: CRBGBX

MANF: MICRO MEASUREMENTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.002		01.02	10.10 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00005.68	

63174 LAMIN EPOXY/GLASS/RL4389 COATED GID: COBGGD

MANF: NASA/JPL
RM INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.015			04.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00801.10	24H-125F-

63179 LAMIN EPOXY/GLASS/SCOTCHCAST 251 GID: COBGIA

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.110			11.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05164 LAMIN EPOXY/GLASS/SOLITHANE COATED GID: COBGXX

MANF: THIOKOL

SPEC: STM-K776 T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.062			00.50	NONE
C	1	020.9	014.7	0.062			08.10	NONE
I	1	023.8	014.5	0.022		00.25	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63159 LAMIN EPOXY/GLASS/URALANE 5750 COATED GID: COBGIA

MANF: U O PRODUCTS

SPEC: MIL-P-13949

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.065		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005813 9

63159 LAMIN EPOXY/GLASS/URALANE 5750 COATED (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.065			04.10	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

63160 LAMIN EPOXY/GLASS/URALANE 5753 COATED GID: COBGIA

MANF: U O PRODUCTS SPEC: MIL-P-13949

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.100		00.00	00.00	NONE
A	1	020.9	014.7	0.100			03.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06475 LAMIN EPOXY/GRAPHITE GID: COBGGF

MANF: FIBERITE SPEC: MB0130-001 MB0130-087T3C4
HERCULES MB0130-160T2C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.017		00.00	00.00	NONE
A	1	020.9	014.7	0.017			05.50	SMALL
A	1	023.8	014.5				03.00	NONE
A	1	030.0	009.0	0.082		00.00	00.00	NONE
A	1	030.0	009.0	0.076		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.3E-6	.92	.01	.28	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	97.50	

60956 LAMIN EPOXY/GRAPHITE 3501/AS GID: DTGFBG

MANF: NARMCO SPEC: MB0130-087

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.012		00.50	12.00 T	NONE
I	1	023.8	014.5	0.022		00.30	12.00 T	NONE
I	1	023.8	014.5	0.033		00.20	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.77	.01	.00	5H-379F- 24H-261F-0psiaVACUUM

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.48	

60962 LAMIN EPOXY/GRAPHITE 5208/T300 GID: COEHBG

MANF: NARMCO SPEC: MB0130-087

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.009		00.700	12.00 T	NONE
I	1	023.8	014.5	0.017		00.400	12.00 T	NONE
B	1	023.8	014.5	0.024		00.200	08.90	NONE
A	1	023.8	014.5	0.038			02.20	NONE
A	1	025.9	014.3	0.095			04.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.0E-6	.41	.13	.20	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.76	

80114 LAMIN EPOXY/GRAPHITE COATED WITH SMOOTH TEDLAR

MANF: HERCULES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	99.45	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005814 0

80115 LAMIN EPOXY/GRAPHITE COATED WITH TEXTURED TEDLAR

MANF: HERCULES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	106.38	

TOXICITY

05765 LAMIN EPOXY/GRAPHITE F263 GID: COGFBG

MANF: HEXCEL

SPEC: TB0130-001

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.075		00.11	12.00	T MOD
X	1	020.9	014.7	0.071		00.12	12.00	T MOD
X	1	020.9	014.7	0.057		00.14	12.00	T MOD
X	1	020.9	014.7	0.072		00.20	12.00	T MOD
X	1	020.9	014.7	0.043		00.15	12.00	T MOD
X	1	020.9	014.7	0.033		00.17	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.2E-7	.68	.01		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

61478 LAMIN EPOXY/GRAPHITE F263 GID: COGFBG

MANF: HEXCEL

SPEC: TB0130-001

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.084			06.30	SMALL
I	1	023.8	014.5	0.084		00.08	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85365 LAMIN EPOXY/GRAPHITE FIBERITE HY-E2030D GID: COBGXX

MANF: COMPOSITE OPTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.055			00.12	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	2.0E-6	.47	.00	.09	

ODOR

RT	RT	WEIGHT	CURE
	K	29.80	

TOXICITY

06040 LAMIN EPOXY/GRAPHITE GY70/E42 GID: COBGGF

MANF: U S POLYMERIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.014			01.90	MOD
X	2	025.9	014.3	0.016			00.50	NONE
X	1	025.9	014.3	0.016		00.51	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00009.95	

TOXICITY

60673 LAMIN EPOXY/GRAPHITE GY70/X30 GID: COBGEH

MANF: GENERAL DYNAMICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.067		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.46	.01	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005815 2

63518 LAMIN EPOXY/GRAPHITE HE1034E GID: COBGGF
MANF: FIBERITE

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.041		00.07	02.10	SMALL	No test data		No test data						

THERMAL VACUUM STABILITY						ODOR			TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE	
C	1.0E-6	1.49	.08	.65	.5H-392F-	No test data			

61063 LAMIN EPOXY/GRAPHITE HMF/34 GID: COGEBG
MANF: FIBERITE

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
I	1	020.9	014.7	0.005		00.27	12.20	T SMALL	No test data		No test data						

60964 LAMIN EPOXY/GRAPHITE HMF330B/34 GID: COFOXX
MANF: FIBERITE

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
I	1	020.9	014.7	0.037		00.25	12.00	T SMALL	No test data		No test data						
I	1	020.9	014.7	0.037		00.25	12.00	T SMALL									
I	1	020.9	014.7	0.030		00.28	12.00	T NONE									

THERMAL VACUUM STABILITY						ODOR			TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE	
B	1.0E-6	.90	.05	.00	2H-356F-	No test data			

06296 LAMIN EPOXY/GRAPHITE HMFB3-714H GID: COBGGF
MANF: ROCKWELL

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
C	2	020.9	014.7	0.033		00.00	00.00	NONE	No test data		No test data						
C	1	020.9	014.7	0.033		00.14	09.00	T SMALL									

THERMAL VACUUM STABILITY						ODOR			TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE	
A	4.4E-6	.45	.06			A	K 00020.72		

65548 LAMIN EPOXY/GRAPHITE T50/934 GID: COGFBG
MANF: FIBERITE

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.125		00.00	00.00	NONE	No test data		No test data						
A	1	025.9	014.3	0.240		0.003	00.13	NONE									
A	1	25.9	14.3	.291			00.00	NONE									

THERMAL VACUUM STABILITY						ODOR			TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE	
B	1.0E-6	.40	.09	.00	4H-351F-		K 53.9		

62098 LAMIN EPOXY/GRAPHITE/KEVLAR GID: CRJHBG
MANF: CONVAIR

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7	0.321			08.70	NONE	No test data		No test data						

61144 LAMIN EPOXY/KELVAR E707/KEVLAR 120 GID: BBBGJH
MANF: U S POLYMERIC

THERMAL VACUUM STABILITY						ODOR			TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE	
B	6.0E-6	1.72	.01	1.13	6H-350F-0psiaVACUUM	No test data			

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005816 4

61937 LAMIN EPOXY/KEVLAR 120 GID: COBGJH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	1.25	.00		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05028 LAMIN EPOXY/KEVLAR 570PRO/49-181 KEVLAR GID: COBGXX

MANF: NARMCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.028			00.10	NONE
C	1	020.9	014.7	0.028		00.21	05.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.60	.00	.00	2H-345F-

ODOR

RT	RT WEIGHT	CURE
A	K 00134.86	

TOXICITY

62482 LAMIN EPOXY/KEVLAR CE306/281 GID: COBGJH

MANF: FERRO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	1.76	.04		1H-250F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60489 LAMIN EPOXY/KEVLAR CE342 GID: COJHCK

MANF: HUGHES AIRCRAFT

SPEC: HMS 16-2074 HMS 20-2075

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.541		00.12	09.50	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05590 LAMIN EPOXY/KEVLAR CE9010/7781 GID: COBGIA

MANF: FERRO

SPEC: MB0130-105T8B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.018			04.10	NONE
I	1	023.8	014.5	0.009		00.64	12.00	T NONE
I	1	023.8	014.5	0.017		00.38	12.00	T NONE
B	1	023.8	014.5	0.048		00.12	07.00	NONE
A	1	030.0	009.0	0.043			05.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.4E-6	.28	.00		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.11	

TOXICITY

62055 LAMIN EPOXY/KEVLAR DSX501/181 KEVLAR 49 GID: CKBGJH

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.018			00.20	NONE
B	1	023.8	014.5	0.018			01.60	NONE
B	1	025.9	014.5	0.018			11.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62549 LAMIN EPOXY/KEVLAR DUCT GID: COARBG

MANF: ROCKWELL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.5	0.030		00.00	00.00	NONE
X	1	023.8	014.5	0.030			02.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61559 LAMIN EPOXY/KEVLAR E42 GID: COBGGF

MANF: U S POLYMERIC

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005817 6

61559 LAMIN EPOXY/KEVLAR E42 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.021			01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	.42	.00		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62481 LAMIN EPOXY/KEVLAR E719/12 KEVLAR 181 GID: COBGJH

MANF: U S POLYMERIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	1.95	.02		1H-250F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61785 LAMIN EPOXY/KEVLAR E720E FR 49-120 GID: COCDBG

MANF: U S POLYMERIC SPEC: MB0130-127T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.012		00.10	12.00 T	NONE
I	1	023.8	014.5	0.015		00.38	12.00 T	NONE
I	1	023.8	014.5	0.009		00.06	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.7E-6	1.38	.00		

ODOR

RT	RT WEIGHT	CURE
A	B 00020.01	1.5H-350F-

TOXICITY

61156 LAMIN EPOXY/KEVLAR F155 GID: COBGJH

MANF: HEXCEL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	1.35	.02		16H-250F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61267 LAMIN EPOXY/KEVLAR F161 GID: CRBGFV

MANF: HEXCEL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.24	.00	.00	1.3H-351F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61537 LAMIN EPOXY/KEVLAR F164-1/181 GID: COBGJH

MANF: HEXCEL SPEC: MB0130-127T8

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.017			02.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60959 LAMIN EPOXY/KEVLAR F164/120 KEVLAR 49 GID: COBGJH

MANF: HEXCEL SPEC: MB0130-127T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.018			00.10	NONE
C	1	023.8	014.5	0.018		00.05	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61788 LAMIN EPOXY/KEVLAR F164/KEVLAR 49 GID: COARBG

MANF: GENERAL DYNAMICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.4E-6	1.04	.01		2H-350F-0psia1E-5

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005818 8

85488 LAMIN EPOXY/NOMEX R398/F263
MANF: TULSA DIV

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.800			00.60	NONE	No test data		No test data							

64814 LAMIN EPOXY/PC12-007M COATED GID: COBGCQ
MANF: VOUGHT SPEC: MIL-I-46058TYER

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.060			00.70	NONE	No test data		No test data							

06263 LAMIN EPOXY/PHENOLIC GID: COGBXX
MANF: SPEC: MIL-R-9299
....NO TEST DATA AVAILABLE....

00013 LAMIN EPOXY/PHENOLIC M602 GID: COABXX
MANF: NATIONAL STARCH AND CHEMICAL SPEC: MB0120-032
....NO TEST DATA AVAILABLE....

63175 LAMIN EPOXY/PLASTIC GID: COBGXX
MANF: FERRO

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.040			04.00	SMALL	No test data		No test data							
A	1	025.9	014.3	0.040			04.00	SMALL										

61157 LAMIN F120-150-1P20 GID: COBXFV
MANF: HEXCEL

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.089			01.10	NONE	No test data		No test data							

02008 LAMIN F131-21 GLASS/SILICONE GID: CRGDCK
MANF: COAST MFG & SUPPLY SPEC: LB0130-105
....NO TEST DATA AVAILABLE....

60280 LAMIN F161-1581/F50
MANF: HEXCEL
....NO TEST DATA AVAILABLE....

05366 LAMIN F161-173G/7781 EPOXY/GLASS GID: COBGIA
MANF: HEXCEL SPEC: MB0130-105T8BC1

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	2	023.8	014.5	0.099			00.10	NONE	No test data		No test data							
A	1	023.8	014.5	0.099			02.60	NONE										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
I	2.8E-7	.26	.01		

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
A	K 00020.47	

05138 LAMIN F161-173G/7781/HS8171 GID: COXXXX
MANF: HEXCEL

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.39	.08	.00	1.3H-351F-

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005819 T

62199 LAMIN F164/181 KEVLAR-49 GID: COBGJH
MANF: HEXCEL SPEC: MB0130-127T3
ROCKWELL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00035.18	

TOXICITY

05280 LAMIN FIBERFRAX T30LR (INORGANIC) GID: COXXXX
MANF: DUPONT SPEC: MB0130-134
....NO TEST DATA AVAILABLE....

61954 LAMIN FIBERGLASS TA88 GID: CRFVXX
MANF: T A MFG CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.067			04.20	SMALL
X	1	033.0	014.3	0.067		00.07	06.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	K 00020.27	

TOXICITY

61856 LAMIN FIBERITE 1 GID: CRFVXX
MANF: SPAR AEROSPACE SPEC: MIL-R-9300

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.054			04.40	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.7E-7	.48	.04		1.5H-261F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60064 LAMIN FIBERITE MX2652 GID: CRXXXX
MANF: U S POLYMERIC
....NO TEST DATA AVAILABLE....

60063 LAMIN FIBERITE MX4926 GID: CRXXXX
MANF: U S POLYMERIC
....NO TEST DATA AVAILABLE....

63177 LAMIN FIBERITE MXB5004/1581 GID: CRCDXX
MANF: FIBERITE SPEC: STM0530-03

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.041			03.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60070 LAMIN FIBERITE MXB6020 GID: CRXXXX
MANF: U S POLYMERIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.01	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05487 LAMIN FIBERITE MXB7701 GID: AZBGIA
MANF: FIBERITE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.204			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.4E-6	.59	.03		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005820 6

85419 LAMIN FIBERITE T50/934 GRAPHITE WITH ADHESIVE FILM HT424 AND PRIMER GID: COXXXX
MANF: FIBERITE SPEC: HMF 133/34 MMM-A-132T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.291			00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62029 LAMIN FM5055 CARBON PHENOLIC GID: COFOFG
MANF: U S POLYMERIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.195		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-7	3.50	.00		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61179 LAMIN FORTIN CORE 1111 GID: COMCFX
MANF: FORTIN CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.006			00.10	SMALL
A	1	030.0	009.0	0.006			01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.07	.00		

ODOR

RT	RT WEIGHT	CURE
A	00020.90	

TOXICITY

61208 LAMIN FORTIN CORE 2121 GID: COFXMC
MANF: FORTIN CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.007			01.50	SMALL
A	1	030.0	009.0	0.007			00.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.04	.01		

ODOR

RT	RT WEIGHT	CURE
A	00020.70	

TOXICITY

62708 LAMIN FORTIN CORE 2222 GID: COFXMC
MANF: FORTIN CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.009			01.30	NONE
A	1	030.0	009.0	0.009			00.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	-.04	.00		

ODOR

RT	RT WEIGHT	CURE
A	00019.71	

TOXICITY

05382 LAMIN G1065M-28-S12 WITH COPPER GID: CRBGXX
MANF: WESTINGHOUSE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.063		00.00	00.00	NONE
A	1	023.8	014.5	0.063			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60981 LAMIN G7-832 GID: COXXXX
MANF: NVF CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.263		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005821 8

60981 LAMIN G7-832 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.8E-6	.51	.00	.04	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

06431 LAMIN GILLFLOOR 5007A BALSA/GLASS GID: COGXXX

MANF: MCGILL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	1.100		00.12	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64447 LAMIN GLASS CLOTH GID: COIAXX

MANF: G & D INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.041			06.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.71	.27	.63	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

69944 LAMIN GRAPHITE HFT-G HONEYCOMB CORE

MANF: HEXCEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	2.000			02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.07	.02	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	K 21.403	

06565 LAMIN GRAPHITE/POLYIMIDE GID: COGFXX

MANF: FIBERITE SPEC: MB0130-152T1C1

....NO TEST DATA AVAILABLE....

05578 LAMIN GT100/GT420/GT10/QR43117 GID: COBGCD

MANF: SINGER KEARFOTT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.073			00.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00225.23	20H-158F- 5H-176F-

61166 LAMIN HMS/934/SOMA30 EPOXY GID: COBGXX

MANF: FIBERITE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.2E-6	1.09	.00	.51	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05020 LAMIN HMS/X904 GID: COBGXX

MANF: FIBERITE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000			0.032	02	20
X	PNEU	1500			0.032	01	01
B	PNEU	500			0.032	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	5.6E-6	.39	.01		4H-375F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
	X 00015.41	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005822 T

60487 LAMIN HONEYCOMB LEASAT ANTENNA GID: COJHBV

MANF: HUGHES AIRCRAFT SPEC: HMS 16-2074 HMS 20-1658

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.260		00.14	11.30	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61719 LAMIN KERIMID 601/KEVLAR 49-181 GID: COBGCD

MANF: GENERAL DYNAMICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.2E-6	1.04	.02		SEE TEST REPORT

ODOR

RT	RT	WEIGHT	CURE
A	V	00020.70	SEE TEST REPORT

TOXICITY

62485 LAMIN KEVLAR 143/E788 GID: COJHXX

MANF: U S POLYMERIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.023		00.37	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-7	1.94	.00		4H-350F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

61728 LAMIN KEVLAR 49-181/SKYBOND 703 GID: COCDXX

MANF: GENERAL DYNAMICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.2E-6	.85	.00		SEE TEST REPORT

ODOR

RT	RT	WEIGHT	CURE
A	V	00020.52	SEE TEST REPORT

TOXICITY

62560 LAMIN KEVLAR 49/32 EPOXY GID: BBJHXX

MANF: STRUCTURAL COMPOSITES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	2.54	.03	.24	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

06083 LAMIN KEVLAR 49/LY8061 EPOXY GID: COJHBG

MANF: MCDONNELL DOUGLAS SPEC: PS 14106

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.046			00.10	NONE
C	1	020.9	014.7	0.046			01.00	NONE
X	1	023.8	014.5	0.030		00.25	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.79	.02	.00	24H-257F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

62559 LAMIN KEVLAR 49/SKYBOND 703 GID: CRCDXX

MANF: GENERAL DYNAMICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.85	.00	.00	.5H-240F-0psiaVACUUM. TEMP WAS RAISED 3 DEGREES PER MINUTE. .5H-270F-0psiaTEMP WAS RAISED 1 DEGREE PER MINUTE. 1H-350F-0psiaTEMP WAS RAISED 1 DEGREE PER MINUTE. COOLED TO BELOW 175 BEF ORE REMOVING VACUUM BAG.

ODOR

RT	RT	WEIGHT	CURE
A	B	00020.48	SEE TEST REPORT

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005823 1

61805 LAMIN KEVLAR/PR1660/10% PHOSGRD GID: COARCQ

MANF: ROCKWELL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.4E-6	2.87	.60		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61953 LAMIN KYDEX ACRYLIC/PVC ALLOY GID: COAKAE

MANF: ROHM & HAAS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.126			02.70	NONE
X	1	033.0	014.3	0.126		00.05	07.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00038.22	

TOXICITY

62176 LAMIN LEXAN/TEDLAR GID: COCAEF

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.050		00.04	07.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	0Q019.52	

TOXICITY

64979 LAMIN MELAMINE/GLASS G5-813 GID: FJARHK

MANF: NVF CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.030			01.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

01716 LAMIN MELAMINE/GLASS G9-818 GID: FJARHK

MANF: NVF CO

SPEC: MIL-P-15037TGME

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.029			01.30	NONE
A	1	023.8	014.5	0.050			00.90	NONE
A	1	030.0	009.0	0.030			02.10	NONE
A	1	030.0	010.0	0.034			03.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.4E-6	2.74	.00	.00	

ODOR

RT	RT WEIGHT	CURE
A	00022.00	

TOXICITY

61690 LAMIN MICAPLY EG818T GID: COBGIA

MANF: MICA CORP

SPEC: MIL-P-13949

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.065			01.50	SMALL
A	1	025.9	014.3	0.063			04.00	SMALL
I	1	030.0	010.4	0.063		00.12	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.4E-6	.35	.00	.16	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

03422 LAMIN MYLAR/PROPYLENE GID: COXXXX

....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005824 3

Information Handling Services, 2000

05485 LAMIN NARMCO 3203-1581 EPOXY GID: COBGXX

MANF: NARMCO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.32	.01	.00	1.5H-261F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63158 LAMIN ON STEEL SUB WITH P223 GID: FBXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.015	0.031		01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05985 LAMIN OVERCOAT WITH 1B31/FC721 GID: COBGCQ

MANF: SINGER KEARFOTT SPEC: MIL-P-13949

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.054			04.40	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
V	00048.05	

TOXICITY

69977 LAMIN PC BOARD #H3C WMCKT BRD DEVELOPMENT GID: COXXXX

MANF: ROTRONIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	30.554	

TOXICITY

62239 LAMIN PHENOLIC 2210/A1100/1581 GID: CRBXXX

MANF: FERRO SPEC: MB0130-004T6C2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.019			01.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60104 LAMIN PHENOLIC/COTTON

MANF: SYNTHANE-TAYLOR CORP SPEC: STW4-2748

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.600		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.9E-6	04.87	00.01	03.62	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60075 LAMIN PHENOLIC/COTTON TYPE FBM GID: BBFSXX

MANF: SPEC: MDA-151ET MIL-P-15035C

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.07	.01	.00	

ODOR

RT	RT WEIGHT	CURE
A	00022.25	

TOXICITY

03428 LAMIN PHENOLIC/GLASS GID: COBXIA

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.37	.06	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20879 LAMIN PHENOLIC/GLASS GID: CRBXXX

MANF: AQM SPEC: F 508/181

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.356			00.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005825 5

20879 LAMIN PHENOLIC/GLASS (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.68	.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

02893 LAMIN PHENOLIC/GLASS F508 VOLAN A/7781 GID: FJBXIA

MANF: U S POLYMERIC SPEC: MB0130-004C1T6

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.025			01.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.01	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05131 LAMIN PHENOLIC/NYLON GID: COBSBX

MANF: GENERAL ELECTRIC SPEC: MIL-P-15047NPG

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.18	.00		264H-260F-
C	1.4E-6	2.94	.01	.91	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

02343 LAMIN PHENOLIC/PAPER GID: CTBXXX

MANF: GENERAL ELECTRIC
SYNTHANE-TAYLOR CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.035			00.10	NONE
X	1	023.8	014.5	0.035		00.15	12.00	T MOD
X	1	025.9	014.3	0.091		00.07	12.00	T MOD
X	2	030.0	010.0	0.031		00.09	12.00	T MOD
X	1	030.0	010.0	0.031		0.3	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	3.55	.00		

ODOR

RT	RT WEIGHT	CURE
	A 00010.13	

TOXICITY

60251 LAMIN PHENOLIC/S-GLASS CLOTH GID: COBXXX

MANF: SPEC: USB-MS-1004

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.64	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60254 LAMIN PLASTIC THERMOSETTING GID: COXXXX

....NO TEST DATA AVAILABLE....

60238 LAMIN POLYESTER GLASS 181/150 HT GID: COCBXX

....NO TEST DATA AVAILABLE....

20550 LAMIN POLYESTER/GLASS HETRON 92 GID: CRXXXX

MANF: HAMILTON STANDARD SPEC: SVHS 8091T12

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.135		00.03	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.74	.02		

ODOR

RT	RT WEIGHT	CURE
	A 00020.31	

TOXICITY

MSFC-HDBK-527 REV F 9999942 0005826 7

Information Handling Services, 2000

64075 LAMIN POLYETHYLENE/PLASTIC GID: COCCXX
MANF: PLICON CORPORATION

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00041.13	

TOXICITY

61372 LAMIN POLYETHYLENE/SARANEX 23 GID: BPCFXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.047		00.09	10.00	T MOD
X	1	025.9	014.3	0.047		00.37	10.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-7	.18	.00		

ODOR

RT	RT WEIGHT	CURE
A	K 00020.23	

TOXICITY

61451 LAMIN POLYIMIDE HI3003 GID: COCDIA
MANF: HOWE IND SPEC: MB0130-125

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.014			03.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

02432 LAMIN POLYIMIDE/GLASS GID: COCDGD
MANF: DUPONT SPEC: MB0130-081

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.85	.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05124 LAMIN POLYIMIDE/GLASS GID: COCDIA
MANF: HEXCEL SPEC: MB0130-104AT8B MB0130-104T8

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.017			00.10	NONE
C	1	023.8	014.5	0.017		00.30	12.00	T NONE
A	1	023.8	014.5	0.078			04.70	SMALL
A	1	023.8	014.5	0.095			02.00	SMALL
A	1	023.8	014.5	0.055			04.50	SMALL
C	2	030.0	010.0	0.130		00.00	00.00	NONE
C	1	030.0	010.0	0.130		00.10	12.00	T SMALL

FSC

RT	FLUID NAME
	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	00.71	00.00	00.00	

ODOR

RT	RT WEIGHT	CURE
A	V 00020.35	4H-475F-POST CURED AT RT TO 475F/4H-475F 4H-475F-

TOXICITY

05161 LAMIN POLYIMIDE/GLASS GID: COCDIA
MANF: MICA CORP SPEC: MB0130-125

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.120			00.30	SMALL
I	2	100.0	016.5	0.120		00.01	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.2E-6	.51	.01		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.20	

TOXICITY

05316 LAMIN POLYIMIDE/GLASS GID: COIACD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.77	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005827 9

61428 LAMIN POLYIMIDE/GLASS GID: COCDIA
MANF: ATLANTIC LAMINATES SPEC: MIL-P-13949/10/13 MIL-P-13949GI

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.058			01.20	SMALL
A	1	025.9	014.3	0.066		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.29	.00	.00	1H-257F-0psiaVACUUM 2H-356F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00020.06	

64096 LAMIN POLYIMIDE/GLASS GID: COCDIA
MANF: DAINIPPON INK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.77	.00	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00070.70	

05679 LAMIN POLYIMIDE/GLASS CP2252/7781 GID: CKCDIA
MANF: FERRO SPEC: MB0130-104T8B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.019		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05207 LAMIN POLYIMIDE/GLASS CPI2252/7781 GID: COCDIA
MANF: FERRO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.057		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.2E-5	.36	.00		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.06	

05636 LAMIN POLYIMIDE/GLASS F174 GID: COCDIA
MANF: HEXCEL SPEC: MB0130-140T6

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.018			00.10	NONE
A	1	023.8	014.5	0.072			00.10	NONE
A	1	023.8	014.5	0.020			00.10	NONE
A	1	023.8	014.5	0.067		00.00	00.00	NONE
A	1	030.0	009.0	0.019			01.40	NONE
A	1	030.0	009.0	0.068		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.8E-7	.51	.00		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00048.00	

61890 LAMIN POLYIMIDE/GLASS F178/7781 GID: COCDIA
MANF: HEXCEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.058			01.60	NONE
A	1	023.8	014.5	0.030			01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61453 LAMIN POLYIMIDE/GLASS HI3000 GID: COCDIA
MANF: HOWE IND SPEC: MB0130-125

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.23	.02	.10	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00020.60	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005828 0

61452 LAMIN POLYIMIDE/GLASS MICAPAK PG402T GID: COCDIA
MANF: MICA CORP SPEC: MB0130-125

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.014			02.70	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62099 LAMIN POLYIMIDE/RESIN X PLY GID: COCDXX
MANF: HEXCEL SPEC: MB0130-104T8B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.066			11.60	NONE
I	1	023.8	014.5	0.074			09.40	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61454 LAMIN PRINTED WIRING BOARD /DC3140 COATED GID: FCXXXX
MANF: DOW CORNING
INTERCIRCUITS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.076			01.00	SMALL
A	1	030.0	010.0	0.075			01.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61726 LAMIN PYRALIN 3001/KEVLAR 49-181 GID: COCDXX
MANF: GENERAL DYNAMICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.2E-6	.57	.01		SEE TEST REPORT

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.92	SEE TEST REPORT

61727 LAMIN PYRALIN 3003/KEVLAR 49-181 GID: COCDXX
MANF: GENERAL DYNAMICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.2E-6	.72	.02		SEE TEST REPORT

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.37	SEE TEST REPORT

65313 LAMIN SAFE-T-POXY GID: COBGIA
MANF: APPLIED PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.130		00.09	11.10	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00022.83	

62028 LAMIN SCOTCHPLY 1009-36 EPOXY GID: COBGXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.127		00.03	03.90	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.83	2.14	.00	1H-300F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

02860 LAMIN SHIM/POLYESTER ADHESIVE GID: COCBXX
MANF: BLAISDELL MFG INC SPEC: MIL-S-22499

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.048		00.00	00.00	NONE
X	1	030.0	009.0	1.200		00.04	07.20	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70	0.048	0	20
B	MECH	1500	72	70	0.048	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005829 2

02860 LAMIN SHIM/POLYESTER ADHESIVE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.002			04.30	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.0E-7	2.41	.09		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
V	00020.00	

01883 LAMIN SILICONE/GLASS GID: CRCKGD

MANF: SYNTHANE-TAYLOR CORP SPEC: MIL-P-997GSG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.030			00.10	NONE
A	1	030.0	009.0	0.033			00.70	NONE
A	1	040.0	008.0	0.032			00.90	NONE
A	1	050.0	008.0	0.032			00.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.09	.02	.00	1H-430F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00009.91	

05136 LAMIN SILICONE/GLASS GID: COCKIA

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.12	.42	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

85400 LAMIN STYRENE/GLASS REXOLITE 2200

MANF: NORPLEX OAK INDUSTRIES SPEC: MIL-F-66651/1

....NO TEST DATA AVAILABLE....

01879 LAMIN SYNTHANE G9 NATURAL GID: COARIA

MANF: SYNTHANE-TAYLOR CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.050			00.90	SMALL
X	1	030.0	010.0	0.034			03.60	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06006 LAMIN TEFLON TFE/GLASS GID: COCNIA

MANF: SPEC: MIL-P-13949GA

....NO TEST DATA AVAILABLE....

61317 LAMIN TEXTOLITE 11508 GID: COARIA

MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.9E-7	2.13	.01		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

64900 LAMIN TEXTOLITE 11546 GID: COASIA

MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.64	.01	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

05321 LAMIN THORNEL 300/934 GRAPHITE/EPOXY GID: COGFBG

MANF: FIBERITE SPEC: TB0130-001
MCDONNELL DOUGLAS
ROCKWELL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.060			00.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005830 9

05321 LAMIN THORNEL 300/934 GRAPHITE/EPOXY (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	020.9	014.7	0.055		00.19	21.00	T NONE
A	1	020.9	014.7	0.131		00.00	00.00	NONE
I	1	023.8	014.5	0.025		00.30	12.00	T NONE
C	2	023.8	014.5	0.062		00.00	00.00	NONE
C	1	023.8	014.5	0.062		00.36	11.87	SMALL
X	1	023.8	014.5	0.089		00.05	08.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.58	.00	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.99	

85482 LAMIN THORNEL P75 2K/ERLX 1962 QUASI ISOTROPIC LAYUP GID: COXXXX

MANF: AMOCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.2	0.125		0.003	00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85426 LAMIN THORNEL P75 2K/ERLX 1962 UNIDIRECTIONAL POLYMERIC RESIN/CARBON GID: COXXXX

MANF: AMOCO SPEC: P/N 38100-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.2	0.040		00.09	10.0	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61982 LAMIN URALANE 5570 COATED WITH FC721 GID: BDBFIA

MANF: WESTINGHOUSE SPEC: MIL-P-13949 MIL-P-55640

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00162.28	

20567 LAMIN VANOXY 128/VERSAMID 140F GID: COXXXX

MANF: GENTEX CORP

....NO TEST DATA AVAILABLE....

63180 LAMIN VITON B50/KEVLAR 49/181 GID: COJHXX

MANF: MCDONNELL DOUGLAS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.063			02.30	SMALL
A	1	023.8	014.5	0.110			01.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61800 LAMIN/EPOXY/EPOCAST 1468/FYROL FR2 GID: COBGXX

MANF: ARROWHEAD PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.065		00.42	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20547 LAMIN/EPOXY/GLASS EPON 815/GLASS 7781/DTA GID: CRBGXX

MANF: SHELL CHEMICAL SPEC: SVHS 8091T8

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.107		00.13	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.85	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.92	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005831 0

20548 LAMIN/EPOXY/GLASS/EPON 815/GLASS 112/DTA GID: CRBGXX

MANF: SHELL CHEMICAL SPEC: SVHS 8091T9

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.115		00.13	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.68	.00		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00019.87	

62056 LAMIN/EPOXY/KEVLAR K720FR/KEVLAR 49-181 GID: CKBGJH

MANF: U S POLYMERIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.021			02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63872 LAMINATED SHIM STOCK GID: CDGGXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.33	.00	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00157.70	

20421 LAMP INCANDESCENT GLASS/METAL

....NO TEST DATA AVAILABLE....

20224 LAQUER YELLOW GID: ASAYXX

MANF: SCHRADER SPEC: MS20813

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00043.32	

61209 LBWPD NOMEX COVERED GID: FCXXXX

MANF: ILC DOVER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	1.800			02.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.72	.04	.43	2.5H-165F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

60828 LEAD TAXCHEM MARKING 200 BLUE GID: FCXXXX

MANF: CUTTERS EXCHANGE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.4E-6	2.41	.38	.69	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00019.76	

61635 LEAD TAXCHEM MARKING 200 GREEN GID: FCXXXX

MANF: CUTTERS EXCHANGE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.4E-6	2.12	.35	.36	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00019.66	

62833 LEAK DETECTOR SHERLOCK 5 SEC GID: BVXXXX

MANF: WINTON PRODUCTS SPEC: B20808 MIL-L-25567C

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	72	-297	0.050	0	80

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005832 2

62337 LEATHER CHAP LIGHT WEIGHT GID: CVXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.06	

TOXICITY

20571 LEATHER COWHIDE BLACK 3 OZ GID: CWXXXX

MANF: BERMAN LEATHER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.057			00.10	NONE
X	1	025.9	014.3	0.057		00.12	12.00 T	MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.4E-6	16.52	2.25		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.78	

TOXICITY

20321 LEATHER DEERSKIN GID: CVXXXX SPEC: ST10L069-01

MANF: ELTON LEATHER CORP
THURLOW GLOVE CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.050		00.13	11.90 T	MOD
X	2	025.9	014.3	0.054			07.40	MOD
X	1	025.9	014.3	0.054		00.33	12.00 T	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.8E-6	16.89	1.73		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	50	72	120	0.054	0	20

ODOR

RT	RT	WEIGHT	CURE
	A	00080.00	

TOXICITY

20016 LEATHER GOATSKIN

MANF: AQM

....NO TEST DATA AVAILABLE....

20401 LEATHER NAME PATCHES GID: CVXXXX

MANF: DAVID CLARK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	025.9	014.3	0.042		00.51	06.50 T	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-6	14.30	2.29		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT	WEIGHT	CURE
	X	00003.10	

TOXICITY

20666 LEATHER SUPER SHENE FINISH 2002 GID: AKXXXX SPEC: ST44S1119-01

MANF: TANDY LEATHER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		01.90	NONE
A	1	033.0	014.3	0.001	0.003		02.50	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT	WEIGHT	CURE
A	B	00005.15	SEE MFG

TOXICITY

60683 LED DISPLAY GID: EXXXXX

MANF: DIALIGHT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.040		00.07	03.40 T	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT	WEIGHT	CURE
	K	00021.65	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005833 4

63181 LENS MAKROLON 3900LS GID: EXXXXX
MANF: ESA/ERNO

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	030.0	009.0	0.100			00.10	NONE	No test data	No test data							

63994 LIGHT-WELD 181/ACRYLIC ADHES GID: FMAKXX
MANF: AMERICAN CHEMICAL

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	3.2E-6	5.28	.00	1.51		No test data		

63992 LIGHT-WELD 182 ACRYLIC ADHES GID: FMAKXX
MANF: AMERICAN CHEMICAL

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	3.2E-6	3.49	.05	1.51		No test data		

61113 LINE CASTING WHITE GHOST NYLON GID: EUBSXX
MANF: GLADDING CORP SPEC: ST14N162

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	023.8	014.5	0.025		00.46	12.00 T	NONE	No test data	No test data							
X	1	023.8	014.5	0.025			06.70	NONE									

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-7	1.53	.16			A	A 00020.37	

60398 LINE LACING G-1008
....NO TEST DATA AVAILABLE....

06238 LINER DURALINER NYLON/TFE GID: AHBSCN

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.25	.02	.00		No test data		

06239 LINER FAFTEX NOMEX/TEFLON GID: AHBVCO
....NO TEST DATA AVAILABLE....

05118 LINER FEP/KEVLAR/KAPTON/POLYES
MANF: SHELDAHL
....NO TEST DATA AVAILABLE....

05222 LINER FIBRILOID NOMEX/TFE GID: CZCNEF
MANF: LEAR SIEGLER SPEC: M81934/1-10C016 MIL-B-121E

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	023.8	014.5	0.012		00.41	02.00 T	NONE	No test data	B	MECH	25	72	200	0.011	0	20
A	1	023.8	014.5	0.600		00.00	00.00	NONE									

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.14	.01	.00	12H-351F-	A	A 00059.74	

61262 LINER GLASS CLOTH 120/EPON 815 GID: BFIAXX
MANF: AIR-LOCK INC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.063			01.60	MOD	No test data	No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005834 6

61262 LINER GLASS CLOTH 120/EPON 815 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.063		00.16	12.00 T	MOD
C	2	025.9	014.3	0.021		00.02	08.30	SMALL
C	1	025.9	014.3	0.021		00.67	12.00 T	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.6E-6	1.55	.16	.31	

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00010.32	

61801 LINER HOSE AE 116-8/AE 121-4 GID: CKXXXX

MANF: AEROQUIP

SPEC: ASTM D1457 T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.050	3	11
B	MECH	14.7	72	-297	0.037	0	20
X	PNEU	2000		70	0.050	2	04
I	MECH	3000	72	70	0.050	0	1
X	PNEU	3000		70	0.050	2	08
B	MECH	3500	72	70	0.050	0	20
X	PNEU	4000		70	0.050	1	01
Z	MECH	4000	72	70	0.050	2	23
X	PNEU	4500		70	0.050	1	03
X	PNEU	500		70	0.050	1	20
X	PNEU	5000		70	0.050	1	01

61802 LINER HOSE AE 246-10/667-16 GID: CKXXXX

MANF: AEROQUIP

SPEC: ASTM D1457 T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70	0.052	0	20
B	MECH	14.7	72	-297	0.052	0	20
X	PNEU	1500		70	0.052	2	2
X	PNEU	2000		70	0.052	2	05
X	PNEU	2500		70	0.052	1	2
X	PNEU	3000		70	0.052	1	01
B	MECH	3500	72	69	0.053	0	20
Z	MECH	4000	72	69	0.053	2	17
I	MECH	4500	72	69	0.053	1	2
I	MECH	5000	72	69	0.053	1	4
I	MECH	5500	72	69	0.053	1	6

05221 LINER MILFLOW TEFLON GID: AHCOXX

....NO TEST DATA AVAILABLE....

20674 LIPBALM BLISTIK GID: EYXXXX

MANF: BLISTEX INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00010.76	

20673 LIPBALM CHAPSTICK GID: EYXXXX

MANF: MILLER MORTON CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005835 8

20673 LIPBALM CHAPSTICK (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00009.88	

20675 LIPBALM CONSTANT CARE GID: EYXXXX

MANF: CHESEBROUGH-PONDS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		025.9	014.3					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00013.83	

20624 LIPSTICK NATURAL WONDER GID: EXXXXX

MANF: REVLON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00017.01	

20179 LITHIUM HYDROXIDE INORGANIC

MANF: SPEC: MIL-L-20213

....NO TEST DATA AVAILABLE....

20069 LITHIUM-STEARATE GID: CZARXX

MANF: MATHISON-COLEMAN BEL SPEC: MIL-L-51131

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0			00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00000.17	

05162 LUBE COMPOSITE BEARING KARON GID: AHCNXX

MANF: KAMATICS CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.080		00.12	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.13	.01	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.02	

05055 LUBE COMPOSITE DUROID 5813 GID: AHCNXX

MANF: ROGERS CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.031			00.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1000	72	70	0.033	2	02
Z	MECH	14.7	72	-297	0.033	2	05
X	PNEU	1500		70	0.033	01	20

05061 LUBE COMPOSITE ELEC CONDUCT GID: DAEJXX

MANF: BEMOL CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		70	0.006	1	20
Z	MECH	1500	72	70	0.050	2	03

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.3E-7	.15	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.68	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005836 T

05058 LUBE COMPOSITE FEURALON AW GID: AOGNXX
MANF: ROGERS CORP

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
		025.9	014.3					NONE	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data						A	A	00020.09	

05060 LUBE COMPOSITE PUREBON PBM3
....NO TEST DATA AVAILABLE....

05059 LUBE COMPOSITE WDC120 TO 150
....NO TEST DATA AVAILABLE....

06295 LUBE CPD GRAPHITE/PETROLATUM GID: DBGGXX
MANF: BRAY OIL CO SPEC: MIL-T-5544

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	020.9	014.7	0.007	0.003	00.00	00.00	NONE	No test data	No test data							
C	1	020.9	014.7	0.007	0.003	00.27	12.00 T	NONE									

05723 LUBE DRY GID: DAXXXX
MANF: KAYNAR CORP SPEC: MIL-N-25027

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	00017.51	

05167 LUBE DRY 701 OXYLUBE INORGANIC GID: DAEJXX
MANF: DRILUBE CO

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.001	0.003	00.00	00.00	NONE	No test data	B	PNEU	1500		70	0.001	0	20
										B	MECH	1500	72	70	0.001	0	20

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
B	1.0E-5	.83	.00		1H-350F-	No test data			

65136 LUBE DRY 958-301 TEFLON GID: DAXXXX
MANF: DUPONT

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							B	00004.81	.33H-70F-

05302 LUBE DRY DAG 206 MOS2 INORGANIC GID: DAEJXX
MANF: ACHESON COLLOIDS

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.001	0.003	00.00	00.00	NONE	No test data	B	MECH	14.7	72	-297	0.001	0	20
										B	PNEU	1500		70	0.001	0	20
										B	MECH	1500	72	70	0.001	2	10

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.0E-6	4.97	.19	.00	24H-77F-	A	X	00001.75	1H-350F-

60508 LUBE DRY DAG 213 DISPERSION GID: DAXXXX
MANF: ACHESON COLLOIDS

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005837 1

60508 LUBE DRY DAG 213 DISPERSION (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.39	.01	.06	24H-46F- 16H-302F-

ODOR TOXICITY

RT	RT WEIGHT	CURE
No test data		

60510 LUBE DRY DAG 217 DISPERSION GID: DAXXXX

MANF: ACHESON COLLOIDS

....NO TEST DATA AVAILABLE....

20028 LUBE DRY DAG 250 ORGANIC BINDR GID: DAXXXX

MANF: ACHESON COLLOIDS

....NO TEST DATA AVAILABLE....

20206 LUBE DRY DAG 258 MOS2

MANF: ACHESON COLLOIDS

....NO TEST DATA AVAILABLE....

05088 LUBE DRY DICRONITE DL5 GID: DAMWXX

MANF: DICRONITE SPEC: MB0140-009

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.001	0.003		00.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1500	368	70		0	20
B	MECH	6000	368	70		0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	8.0E-7	.47	.03		

ODOR TOXICITY

RT	RT WEIGHT	CURE
A	X 00000.73	

20461 LUBE DRY DRILUBE 1A GID: CZXXXX

MANF: DRILUBE CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.87	2.73	.00	168H-46F- 24H-151F-

ODOR TOXICITY

RT	RT WEIGHT	CURE
A	X 00002.21	168H-70F- 24H-150F-

05046 LUBE DRY DRILUBE 6A GID: DAEJXX

MANF: DRILUBE CO SPEC: MIL-L-46010
SANDSTROM PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		00.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		70	0.003	01	01
X	PNEU	1500		70	0.003	1	1
Z	MECH	1500	72	70	0.003	1	02
Z	MECH	1500	72	70	0.003	1	2

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.5E-6	.42	.01		1.5H-450F-

ODOR TOXICITY

RT	RT WEIGHT	CURE
A	X 00002.32	

20161 LUBE DRY DRILUBE 822 GID: CZXXXX

MANF: DRILUBE CO

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005838 3

60331 LUBE DRY DRILUBE 842 GID: DAXXXX
MANF: DRILUBE CO SPEC: MMS-N308A
....NO TEST DATA AVAILABLE....

65187 LUBE DRY DYFLON GID: AHCBCO
MANF: SOUTHWEST PRODUCT CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.8E-6	1.18	.00	.22	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

20368 LUBE DRY ELECTROFILM 1000 MOS2 GID: DAEJXX
MANF: ELECTROFILM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	5500		70		0	20
B	MECH	5500	72	70	0.001	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-7	.09	.04		SEE MFG

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	V 00002.17	SEE MFG

20003 LUBE DRY ELECTROFILM 2006 ORG GID: DAEJXX
MANF: ELECTROFILM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	MECH	14.7	72	-297	0.005	0	20
B	PNEU	1500		70	0.005	0	20
B	MECH	1500	72	70	0.005	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.01	.00	.00	2H-498F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00000.94	2H-500F-

00880 LUBE DRY ELECTROFILM 2306 INORGANIC GID: DAGPXX
MANF: ELECTROFILM

FLAMMABILITY

No test data

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	300	72	70	0.001	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.00	.03	.00	2H-180F-
					2H-399F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

20095 LUBE DRY ELECTROFILM 4306 GID: DAEJXX
MANF: ELECTROFILM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.001	0.003	00.00	00.00	NONE
A	1	100.0	019.0	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	2.05	.00		19H-375F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00000.43	1H-375F-

20002 LUBE DRY ESWA 382 GID: DAEJXX
MANF: E/M LUBRICANTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.001	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005839 5

20002 LUBE DRY ESHA 382 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1500	72	70	0.001	0	20
X	PNEU	1500		70	0.001	1	20
X	PNEU	1500		70	0.005	1	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.9E-6	1.69	.14		1H-350F-

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
A	V	00002.55	1H-350F-

05303 LUBE DRY EVERLUBE 1120-8 GID: DAEJXX

MANF: EVERLUBE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.001	1	07
B	PNEU	1500		70	0.001	0	20
B	MECH	1500	72	70	0.001	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.3E-6	.23	.31		1H-350F-

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
A	X	00000.34	1H-350F-

63943 LUBE DRY EVERLUBE 620C GID: DAXXXX

MANF: EVERLUBE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05072 LUBE DRY EVERLUBE 811 GID: DAEJEI

MANF: E/M LUBRICANTS
EVERLUBE

SPEC: RB0140-017 TY1 ST0140GB0002T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	033.0	010.0	0.001			00.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		350	0.125	0	20
B	PNEU	1000		500	0.001	0	20
A	MECH	1050	72	-297	0.001	0	20
A	MECH	1050	72	280	0.001	0	20
B	PNEU	1050		280	0.001	0	20
A	MECH	2200	72	530	0.001	0	20
B	PNEU	4400		540	0.002	0	20
A	MECH	5500	72	550	0.001	0	20
B	PNEU	5500		550	0.001	0	20
B	MECH	8500	72	500	0.125	0	20
B	MECH	8500	72	70	0.125	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.61	.00	.00	2H-70F- 24H-392F-

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
A	B	8.770	.25H-70F- 2H-150F- 2H-300F-

00881 LUBE DRY EVERLUBE 812 GID: DAEJGF

MANF: E/M LUBRICANTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	MECH	1000	72	70	0.067	0	20
A	MECH	5000	72	700	0.001	0	20
A	MECH	5500	72	500	0.001	0	200
B	PNEU	5500		500	0.001	0	20

MSFC-HDBK-527 REV F 9999942 0005840 1

Information Handling Services, 2000

00881 LUBE DRY EVERLUBE 812 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	MECH	5500	72	500	0.064	0	20
B	PNEU	5500		530	0.057	0	20
A	MECH	8500		500		00	20
A	MECH	900	72	600	0.064	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.7E-6	4.38	.00		2H-150F- 2H-400F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00002.97	.25H-70F- 2H-150F-

06201 LUBE DRY EVERLUBE 823 GID: DAEJXX

MANF: EVERLUBE

....NO TEST DATA AVAILABLE....

05748 LUBE DRY FILM GID: DAEJXX

MANF: AQM

SPEC: MIL-L-81329

....NO TEST DATA AVAILABLE....

63183 LUBE DRY GP1904 GID: CZXXXX

MANF: ACHESON COLLOIDS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003			02.40	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	2.1E-6	1.92	.11	1.16	16H-70F- 1H-150F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00011.81	

20034 LUBE DRY GRAPHITE/BINDER PL94 GID: DAEJXX

MANF: PINCHIN JOHNSON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.6E-6	.51	.20		.25H-70F- 2H-375F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00000.48	.25H-70F-15M-RT/2H-375F 2H-375F-15M-RT/2H-375F

65259 LUBE DRY INLOX 88 GID: DAXXXX

MANF: E/M LUBRICANTS

SPEC: RB0140-007 RE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	600	72	-297	0.005	0	20
B	MECH	600	72	572	0.005	0	20

05718 LUBE DRY INVELCO 33F GID: CZEFXX

MANF: DRILUBE CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005	0.010	01.07	12.00	T SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.0E-7	3.55	2.10		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00010.05	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005841 3

05677 LUBE DRY KALGARD RA MOS2 GID: DAEJXX

MANF: KAL-GARD COATING & MFG SPEC: MIL-L-46010

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.016	0.010		02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.1E-6	.24	.00		1.5H-400F-

ODOR

RT	RT	WEIGHT	CURE
A	B	1.816	1H-70F- 1H-70F- 2H-300F-

TOXICITY

00098 LUBE DRY LUBECO 905 FILM GID: DAEJXX

MANF: LUBECO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	MECH	1000	72	-297	0.004	0	20
A	MECH	1000	72	250	0.004	0	20
B	PNEU	1000		250	0.064	0	20
B	PNEU	1500		70		0	20
B	MECH	3000	72	70	0.000	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.38	.00		

ODOR

RT	RT	WEIGHT	CURE
A	K	00084.88	

TOXICITY

05826 LUBE DRY LUBELOK 5306 GID: DAEJXX

MANF: ELECTROFILM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	1.73	.00		19H-300F-

ODOR

RT	RT	WEIGHT	CURE
A	X	00000.37	

TOXICITY

60980 LUBE DRY LUBELOK 66C FILM GID: DAXXXX

MANF: ELECTROFILM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.8E-6	.89	.00	.76	1H-375F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60913 LUBE DRY LUBRIBOND 220 FILM GID: DAEJXX

MANF: ELECTROFILM SPEC: MIL-L-23398

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.031		00.00	00.00	NONE
A	1	030.0	009.0	0.311		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.08	.20	.00	6H-46F-

ODOR

RT	RT	WEIGHT	CURE
X	X	00004.31	336H-70F-

TOXICITY

60827 LUBE DRY LUBRIBOND 320 GID: DACKXX

MANF: ELECTROFILM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.0E-6				24H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	X	00000.69	24H-70F-

TOXICITY

Information Handling Services, 2000

60827 LUBE DRY LUBRIBOND 320 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					24H-150F-

ODOR TOXICITY

RT	RT WEIGHT	CURE
		24H-150F-

05454 LUBE DRY LUBRIBOND A GID: DAEJXX

MANF: ELECTROFILM

SPEC: MIL-L-23398

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003	00.00	00.00	NONE
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	030.0	010.4	0.210	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	2.20	1.16	.00	168H-46F-

ODOR TOXICITY

RT	RT WEIGHT	CURE
X	V 00003.18	6H-70F-

06114 LUBE DRY LUBRIBOND HT MOS2/ST GID: DAEJXX

MANF: ELECTROFILM

....NO TEST DATA AVAILABLE....

05237 LUBE DRY MICROSEAL 100-1 GID: DAEJXX

MANF: E/M LUBRICANTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	MECH	14.7	72	-297	0.001	0	02
B	PNEU	1500		70	0.001	0	20
B	MECH	1500	72	70	0.001	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR TOXICITY

RT	RT WEIGHT	CURE
A	A 00004.24	

05051 LUBE DRY MICROSEAL 200-1 INORGANIC GID: DAEJXX

MANF: E/M LUBRICANTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	-297	0.064	0	20
B	PNEU	1500	70		0.001	0	20
B	PNEU	1500	200		0.064	0	20
B	PNEU	1500		200	0.064	0	20
B	PNEU	1500		70	0.064	0	20
B	MECH	3300	72	200	0.064	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.0E-6	4.02	.42		

ODOR TOXICITY

RT	RT WEIGHT	CURE
A	X 00000.06	

05050 LUBE DRY MLR66 GID: DAXXXX

....NO TEST DATA AVAILABLE....

05886 LUBE DRY MOLYKOTE 106 MOS2 GID: CZEJXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.45	.00	.00	1H-392F-

ODOR TOXICITY

RT	RT WEIGHT	CURE
No test data		

60347 LUBE DRY MOLYKOTE 3 GID: DBXXXX

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005843 7

06154 LUBE DRY MOLYKOTE 321R GID: CZEJXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	030.0	010.0	0.001		00.00	00.00	NONE
A	1	033.0	014.3	0.001	0.003	00.00	00.00	NONE
A	1	100.0	020.2	0.001	0.003		00.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	7.2E-7	3.67	.00		24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	06630.00	4H-70F-

05328 LUBE DRY MOLYKOTE 33 GID: DBCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.001	0.003		05.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80981 LUBE DRY MOLYKOTE 33 TOX RATE STUDY

MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00019.60	

60865 LUBE DRY MOLYKOTE 3402 MOS2 GID: DAEJXX

MANF: ELECTROFILM

SPEC: MIL-L-46147

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	1.91	.00	1.84	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
No test data		

06146 LUBE DRY MOLYKOTE 44 GID: DBCKXX

MANF: DOW CORNING

SPEC: MIL-L-15719

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.010	0.010	00.85	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.01	1.72	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00013.69	

05719 LUBE DRY MOLYKOTE 505 GID: CZEJXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.002	0.003	01.45	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.0E-7	60.65	12.55		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00006.22	

05455 LUBE DRY MOLYKOTE 55M GID: DAEJFM

MANF: DOW CORNING

SPEC: MIL-G-4343

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.015	0.003	00.00	00.00	NONE
B	1	025.9	014.3	0.015	0.003		09.50	NONE
B	2	025.9	014.3	0.008	0.003	00.00	00.00	NONE
B	1	025.9	014.3	0.008	0.003		09.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005844 9

05455 LUBE DRY MOLYKOTE 55M (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	16.83	8.09	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00003.62	24H-70F-

05823 LUBE DRY MOLYKOTE G GID: DCEJXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002			01.30	NONE
I	1	030.0	009.0	0.003	0.003	01.14	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00019.33	168H-70F-

62554 LUBE DRY MOLYKOTE G-N GID: CZEJXX

MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	37.30	7.40	36.90	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.04	

20394 LUBE DRY MOLYKOTE L GID: DAXXXX

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

20397 LUBE DRY MOLYKOTE M8800 GID: DAXXXX

....NO TEST DATA AVAILABLE....

06172 LUBE DRY MOLYKOTE Z MOS2 INORGANIC GID: DCEJXX

SPEC: MIL-W-7866

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

06247 LUBE DRY MOS2/SILICATE GID: DAEJCK

SPEC: ST0140GB002T1

MANF:

....NO TEST DATA AVAILABLE....

60273 LUBE DRY REDOX U4 FILM GID: DAEJXX

MANF: GENERAL MAGNAPLATE

....NO TEST DATA AVAILABLE....

00597 LUBE DRY NPI14 GID: DAEJXX

SPEC: MIL-L-8937

NPI-14

MANF: NATIONAL PROCESS IND

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.4E-7	4.15	.06		.25H-70F- 1H-300F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00000.91	.25H-70F- 1H-300F-

05044 LUBE DRY NPI425 POLYIMIDE GID: DACDXX

MANF: NATIONAL PROCESS IND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.005		00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	70	0.001	0	20
B	PNEU	1500		70	0.001	0	20
Z	MECH	1500	72	70	0.001	02	15

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.6E-7	.85	.00		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00002.49	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005845 0

20247 LUBE DRY ON METALLIC FASTENERS

....NO TEST DATA AVAILABLE....

00395 LUBE DRY PHENOLIC BINDER N350A GID: DAFJFM

MANF: LUBECO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.005	0.003	00.00	00.00	NONE
A	1	025.9	014.3	0.005	0.003		00.40	NONE
A	1	030.0	009.0	0.005	0.003		00.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.2E-6	1.02	.25	.51	.25H-70F-2H-300F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00001.43	.25H-70F-2H-300F-

20469 LUBE DRY PT101

....NO TEST DATA AVAILABLE....

06115 LUBE DRY SPRAYKOTE MOS2/SILICONE GID: DAEJCK

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

05054 LUBE DRY SPUTTERD FILMS/MOS2

....NO TEST DATA AVAILABLE....

05263 LUBE DRY TIOLUBE 1175 INORGANIC GID: DAEJXX

MANF: TIODIZE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	3300		350	0.005	0	20
B	MECH	3300	72	350	0.005	0	20
B	PNEU	500		70	0.001	0	20
B	MECH	5000	72	70	0.001	0	20
B	PNEU	600		250	0.005	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	3.90	.00	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00002.05	1H-400F-

05869 LUBE DRY TIOLUBE 450 GID: DAXXXX

....NO TEST DATA AVAILABLE....

05520 LUBE DRY TIOLUBE 460 MS21063 GID: DAEJXX

MANF: TIODIZE

SPEC: MIL-L-46010 PD-42 MIL-L-8937

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.84	.00	.00	2H-46F-24H-392F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00006.38	

05638 LUBE DRY TRANSLUBE 20204 GID: DAEJXX

MANF: TRANSLUBE INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.005	0.003		03.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005846 2

05638 LUBE DRY TRANSLUBE 20204 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005	0.003	00.00	00.00	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	9.13	5.88	.00	.5H-250F-

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00011.12	2H-70F- .17H-70F-

05045 LUBE DRY VACKOTE 18.07 GID: DAXXXX

....NO TEST DATA AVAILABLE....

05042 LUBE DRY VITROLUBE 1220 GID: DAHOXX

MANF: NATIONAL PROCESS IND

SPEC: LBO140-004
MPS-MPQ-121A

MPS MPQ 121

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	PNEU	1000		70	0.001	0	01
B	MECH	14.7	72	-297	0.001	0	12
I	PNEU	1500		70	0.001	0	01
I	PNEU	2000		70	0.001	0	01
B	MECH	275	72	-297	0.001	0	20
B	PNEU	275		70	0.001	0	20
B	PNEU	285		200	0.063	0	20
I	PNEU	4500		70	0.001	0	01
I	PNEU	5000		70	0.001	0	01
B	MECH	5700	72	600	0.001	0	20
B	MECH	5700	72	70	0.001	0	20
B	MECH	600	72	600	0.001	0	20
B	PNEU	6000		70	0.001	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00006.31	

05049 LUBE DRY VITROLUBE 2500 INORGANIC GID: DAXXXX

MANF: NATIONAL PROCESS IND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.005	00.00	00.00	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.3E-6	.22	.00	.00	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1500	72	70	0.006	0	20
B	PNEU	1500		70	0.007	0	20

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00002.33	

65255 LUBE EMRALON 314 A/B GID: CZXXXX

MANF: ACHESON COLLOIDS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.002	0.003	00.00	00.00	NONE
C	1	020.9	014.7	0.002	0.003	02.00	12.00	T NONE
I	1	024.5	014.5	0.002	0.003	02.20	12.00	T NONE
I	1	025.9	014.3	0.002	0.003	02.00	12.00	T NONE
A	1	030.0	010.0	0.002	0.003		05.30	SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	7.22	.65	.38	72H-70F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00012.08	72H-70F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005847 4

65532 LUBE EMRALON 320 A/B GID: CZXXXX
MANF: ACHESON COLLOIDS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
C	2	020.9	014.7	0.002	0.003	00.00	00.00		NONE
C	1	020.9	014.7	0.002	0.003	02.00	12.00	T	NONE
I	1	024.5	014.5	0.002	0.003	02.20	12.00	T	NONE
I	1	025.9	014.3	0.002	0.003	02.00	12.00	T	NONE
I	1	030.0	010.0	0.002	0.003	01.90	12.00	T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	4.85	.39	.38	72H-70F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00021.43	72H-70F-

69894 LUBE EMRALON 334
MANF: ACHESON COLLOIDS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	5.0E-6	.90	.01	.56	.5H-300F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

80142 LUBE EMRALON 337
MANF: ACHESON COLLOIDS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.002	0.003		01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.0E-6	.47	.06	.20	.75H-400F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	6.556	.75H-400F-

60333 LUBE ERNO FV0163015
MANF: ERNO PRODUCTS
....NO TEST DATA AVAILABLE....

65029 LUBE EVERLUBE 620 SEE TEST RPT GID: DAEJXX
MANF: E/M LUBRICANTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE
X	HYZE

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.77	.04	.00	1.5H-374F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

05158 LUBE EVERLUBE 620A GID: DWEJEJ
MANF: EVERLUBE SPEC: LB0140-005 MIL-L-8937

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.002	0.003		00.60	NONE

FSC

RT	FLUID NAME
C	HYZE

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	1000.0	30	70	.0004	00	20
C	MECH	1050	35	70	0.001	0	20
B	MECH	14.7	72	-297	0.001	0	20
I	MECH	5500	10	500	0.001	0	20
B	PNEU	8000		70	0.001	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
V	00002.78	1H-375F-

06514 LUBE EVERLUBE 620B1 GID: DAXXXX
MANF: EVERLUBE SPEC: LB0140-005

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005848 6

06514 LUBE EVERLUBE 620B1 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001		00.00	00.00	NONE
A	1	025.9	014.3	0.001		00.00	00.00	NONE
A	1	030.0	009.0	0.001			00.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.31	.00	.00	.16H-70F-THREE BRUSH COAQTS OF THINNED MATERIAL WERE APPLIED. CURED 10 MIN. BETWEEN COATS. .5H-70F-AFTER THIRD COAT WAS APPLIED. 1H-355F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00004.80	SEE MFG

06322 LUBE EXT PRESS PETROLEUM BASE

....NO TEST DATA AVAILABLE....

60409 LUBE FELPRO C100

MANF: FEL PRO INC

....NO TEST DATA AVAILABLE....

60374 LUBE FILM SOLID

SPEC: MIL-L-233983

MANF: SURFKOTE

....NO TEST DATA AVAILABLE....

05568 LUBE FLUOROCARB MS136 TELOMER GID: DAEFXX

SPEC: MIL-L-60326

MANF: MILLER STEPHENSON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	10.42	4.72	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00001.06	168H-70F- 24H-150F-

60274 LUBE FLUOROGEL 865

....NO TEST DATA AVAILABLE....

60252 LUBE FLUOROGLIDE GRADE FB GID: DBXXXX

MANF: CHEMPLAST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	9.49	3.09	.00	168H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

62878 LUBE FLUOROLUBE GRADE FS5 GID: CZXXXX

SPEC: MR-21081

MANF: HOOKER CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	MECH	400	72	-220	0.010	0	20

61889 LUBE GREASE AEROSHELL XSG6249 GID: DBXXXX

SPEC: MIL-G-23827

MANF: SHELL CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.002	0.003	01.50	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00005.65	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005849 8

61665 LUBE GREASE AIRCRAFT GID: DBXXXX
MANF: AEROSPACE LUBRICANTS SPEC: MIL-G-27617CT3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	10000	72	70	0.047	0	20

06297 LUBE GREASE AMDEX 2EP GID: DBXXXX
MANF: AMOCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.010	0.010	00.02	12.00	T NONE
C	1	020.9	014.7	0.010	0.010	01.05	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64917 LUBE GREASE APIEZON H
MANF: BIDDLE CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.86	.16	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05450 LUBE GREASE APIEZON L GID: DBXXXX
MANF: BIDDLE CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.010	0.003	00.09	12.00	T NONE
X	1	030.0	010.0	0.010	0.003	00.70	12.00	T NONE

FSC

RT	FLUID NAME
	HYZE
A	HYZE

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	.34	.29	.00	1H-150F-

ODOR

RT	RT WEIGHT	CURE
	V 00002.04	

TOXICITY

64970 LUBE GREASE APIEZON T GID: DBXXXX
MANF: BIDDLE CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.94	.12	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63790 LUBE GREASE BEACON 325 GID: CZXXXX
MANF: EXXON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	77.40	9.77	.00	

ODOR

RT	RT WEIGHT	CURE
	X 00021.05	

TOXICITY

05067 LUBE GREASE BRAYCO 640AC GID: DBXXXX
MANF: BRAY OIL CO SPEC: MB0140-005 MB0140-005A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		710	0.060	02	02
X	PNEU	2000		710	0.060	01	01
A	MECH	275	72	-297	0.050	0	20
A	MECH	275	72	-297	0.060	0	20
X	PNEU	4000		710	0.060	01	01
X	PNEU	4500		710	0.060	01	01
B	PNEU	500		710	0.060	0	20
X	PNEU	5000		710	0.060	01	01
B	MECH	5500	72	710	0.050	0	20
X	PNEU	5500		710	0.060	02	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.71	.12	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005850 4

05064 LUBE GREASE BRAYCO 800 SERIES

MANF: BRAY OIL CO

....NO TEST DATA AVAILABLE....

61318 LUBE GREASE BRAYCO 814Z GID: DCIEXX

MANF: BRAY OIL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	020.2	0.010		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.3E-6	.65	.00	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00022.34	

05100 LUBE GREASE BRAYCO 815Z FLUORINATED GID: DCBCAP

MANF: BRAY OIL CO

SPEC: LAC34-4553 MB0140-010T1 MB0140-010BT1 ST51B970-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010	0.010		01.50	NONE
A	1	030.0	009.0	0.010	0.010		00.70	NONE

FSC

RT	FLUID NAME
C	HYZE
X	HYZE

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297		0	20
B	MECH	1500	368	70		0	20
B	MECH	4000	368	70		0	01
B	MECH	6000	368	70		0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.25	.01	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.01	

20090 LUBE GREASE BRAYCO 885B GID: CZCBXX

MANF: BRAY OIL CO

SPEC: MIL-L-6085

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.010		00.04	08.10	NONE
C	1	020.9	014.7	0.010		02.90	12.00	T NONE
C	2	023.8	014.5	0.010		00.07	12.00	T NONE
C	1	023.8	014.5	0.010		01.61	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	97.85	10.68		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.01	

60471 LUBE GREASE BRAYCO NPT4 GID: DCXXXX

MANF: BRAY OIL CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	99.56	10.16	10.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

20230 LUBE GREASE BRAYCOTE 236 GID: DBXXXX

MANF: BRAY OIL CO

SPEC: VV-P-236

....NO TEST DATA AVAILABLE....

05128 LUBE GREASE BRAYCOTE 3L-38RP GID: DBEFXX

MANF: BRAY OIL CO

SPEC: LAC34-4554-0200 MB0140-010T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.010			02.50	NONE

FSC

RT	FLUID NAME
	N2O4
C	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	-297	0.050	0	20
B	MECH	1000	72	-297	0.125	0	20
X	PNEU	10000		70	0.050	2	02
B	MECH	10000	72	70	0.060	0	20
B	MECH	11500	72	300	0.050	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005851 6

05128 LUBE GREASE BRAYCOTE 3L-38RP (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	11500	72	70	0.050	0	20
B	MECH	1500	72	-297	0.125	0	20
B	MECH	1500	72	70	0.050	0	20
B	PNEU	1500		70	0.060	0	20
X	PNEU	2000		300	0.060	0	02
X	PNEU	2000		300	0.060	2	02
X	PNEU	2000		540	0.060	2	02
X	PNEU	2000		540	0.060	2	2
X	PNEU	250		540	0.060	2	02
X	PNEU	2500		300	0.060	3	03
X	PNEU	2500		70	0.060	1	09
X	PNEU	3000		540	0.060	1	01
X	PNEU	3000		70	0.002	0	01
X	PNEU	3000		70	0.060	1	04
X	PNEU	3500		300	0.060	3	04
X	PNEU	3500		70	0.060	1	04
X	PNEU	4000		70	0.002	0	01
X	PNEU	4000		70	0.060	2	02
C	MECH	4400	65	540	0.050	0	20
X	PNEU	4400		540	0.060	3	03
X	PNEU	4500		300	0.060	2	02
B	PNEU	500		300	0.060	0	20
X	PNEU	5000		300	0.060	4	09
B	MECH	5500	72	530	0.050	0	10
X	PNEU	5500		540	0.060	6	26
B	MECH	6000	72	530	0.050	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.26	.01	.00	

ODOR

RT	RT	WEIGHT	CURE
A	V	00019.75	

TOXICITY

06138 LUBE GREASE BRAYCOTE 3L-38ZN GID: DBEFXX

MANF: BRAY OIL CO SPEC: MB0110-005

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-7	.07	.00		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

65146 LUBE GREASE BRAYCOTE 600 GID: DBXXXX

MANF: BRAY OIL CO SPEC: L-38-1 MIL-G-276170T4

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.050	0	20

60628 LUBE GREASE BRAYCOTE 601 GID: DCXXXX

MANF: BRAY OIL CO SPEC: MB0140-010T2 MDTSCO 9M03513
SVHS 8523

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.030			01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		300	0.060	0	20
B	MECH	10000	72	70	0.050	0	20
B	MECH	11500	72	300	0.050	0	20
X	PNEU	2000		300	0.060	4	23
B	PNEU	2000		70	0.060	0	20
X	PNEU	2500		70	0.060	3	26
X	PNEU	3500		70	0.060	1	2

MSFC-HDBK-527 REV F 9999942 0005852 8

Information Handling Services, 2000

60628 LUBE GREASE BRAYCOTE 601 (cont)

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
											X	PNEU	4500		70	0.060	1	1
											X	PNEU	5000		70	0.060	2	3

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data							K 00009.10	

65147 LUBE GREASE BRAYCOTE 601 B/L GID: DBXXXX

MANF: BRAY OIL CO

FLAMMABILITY								FSC		OXYGEN COMP							
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	10000	72	70	0.060	0	20

60090 LUBE GREASE BRAYCOTE 6275 GID: DBXXXX

MANF: BRAY OIL CO SPEC: MIL-G-23827

....NO TEST DATA AVAILABLE....

65148 LUBE GREASE BRAYCOTE 804 GID: DBXXXX

MANF: BRAY OIL CO SPEC: MIL-G-27617CT1

FLAMMABILITY								FSC		OXYGEN COMP							
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	14.7	72	-297	0.031	0	20

65149 LUBE GREASE BRAYCOTE 804A GID: DCXXXX

MANF: BRAY OIL CO SPEC: MIL-G-27617CT1

FLAMMABILITY								FSC		OXYGEN COMP							
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	14.7	72	-297	0.060	0	20

65150 LUBE GREASE BRAYCOTE 805 GID: DBXXXX

MANF: BRAY OIL CO

FLAMMABILITY								FSC		OXYGEN COMP							
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B		14.7	72	-297	6.877	0	20

65151 LUBE GREASE BRAYCOTE 805A GID: DCXXXX

MANF: BRAY OIL CO SPEC: MIL-G-27617CT2

FLAMMABILITY								FSC		OXYGEN COMP							
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	14.7	72	-297	0.060	0	20

65070 LUBE GREASE BRAYCOTE 805B2 GID: DCXXXX

MANF: BRAY OIL CO SPEC: MIL-C-27617CT3

FLAMMABILITY								FSC		OXYGEN COMP							
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	14.7	10	-297	0.060	0	20

65152 LUBE GREASE BRAYCOTE 806 GID: DBXXXX

MANF: BRAY OIL CO SPEC: MIL-G-27617CT3

FLAMMABILITY								FSC		OXYGEN COMP							
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	14.7	72	-297	0.020	0	20

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	6.0E-6	1.51	.82	.01		A	A 21.938	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005853 T

65054 LUBE GREASE BRAYCOTE 806A GID: DBXXXX
MANF: BRAY OIL CO SPEC: MIL-G-27617CT3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	72	-297	0.060	1	01

05152 LUBE GREASE CASTALL 800 SILICONE GID: DBCKXX
MANF: CASTALL INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.010	0.010	00.14	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70	0.006	0	20
Z	MECH	1500	72	70	0.050	02	58

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.6E-6	.26	.11	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00002.75	

65257 LUBE GREASE D840924A T1 GID: DBBPXX
MANF: WILLIAM F NYE INC SPEC: MIL-G-27617T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	14.7	10	-297	0.060	0	20

05113 LUBE GREASE DC11 SILICONE GID: DBCKXX
MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data,								

FSC

RT	FLUID NAME
A	HYZE
C	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.40	1.30	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

80051 LUBE GREASE DC111 SILICONE
MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.010	0.010	00.09	11.30	NONE
X	1	030.0	010.0	0.010	0.010	00.40	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.0E-6	.94	.16	.03	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	21.131	

69983 LUBE GREASE DC112 SILICONE
MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.010	0.010	00.09	12.00	T NONE
X	1	030.0	010.0	0.010	0.010	00.40	12.00	T NONE
X	2	032.0	010.0	0.010	0.010	00.09	12.00	T NONE
X	1	032.0	010.0	0.010	0.010	00.40	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.0E-6	.95	.40	.04	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	22.329	

06199 LUBE GREASE DC2 SILICONE GID: DBCKXX
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005854 1

05789 LUBE GREASE DC4 SILICONE GID: DBCKXX

MANF: DOW CORNING SPEC: MIL-S-8660B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.002	0.010	00.02	07.80	MOD
X	1	030.0	010.0	0.002	0.010	00.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	40	70	0.050	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00022.15	

TOXICITY

06210 LUBE GREASE DC970V SILICONE GID: DBCKXX

MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.73	.22	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05647 LUBE GREASE ECCOTHERM TC4 GID: AYCKXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.006			01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.6E-7	5.20	17.00		168H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00031.94	168H-70F-

TOXICITY

65183 LUBE GREASE FOMBLIN Z-LHT GID: DBXXXX

MANF: MONTEDISON SPEC: MIL-G-27617C

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	14.7	10	-297	0.050	0	20

62831 LUBE GREASE HALOCARBON 25-5S GID: DBBEXX

MANF: HALOCARBON PRODUCTS SPEC: MIL-G-47219

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	MECH	400	72	-220	0.050	0	20
B	MECH	5000	72	-297	0.050	0	04
B	MECH	5000	72	68	0.000	0	20
B	MECH	6000	72	-220	0.000	0	20

60155 LUBE GREASE HD CALCIUM 2 GID: DBXXXX

MANF: SPEC: STW5-2942

....NO TEST DATA AVAILABLE....

62396 LUBE GREASE HIGH VACUUM SILICONE GID: DBCKXX

MANF: DOW CORNING
TORAY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.020	0.003		02.20	NONE
A	1	025.9	014.3	0.050	0.010		00.40	NONE
A	1	030.0	010.0	0.051	0.010		00.60	NONE
A	1	30.00	09.00	0.003	0.010		12.0	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	400	40	70	0.050	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.52	.34	.00	

ODOR

RT	RT	WEIGHT	CURE
	K	00022.31	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005855 3

61888 LUBE GREASE HYDROCARBON AF419 GID: DBGGXX

MANF: GULF OIL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00007.79	

05566 LUBE GREASE HYDROCARBON AF903

MANF: GULF OIL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.001	0.003		01.80	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	2.91	1.68	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00011.46	

63703 LUBE GREASE HYLOMAR PL32 GID: AWXXXX

MANF: MARSTON BENTLEY INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.007	0.003	00.35	05.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.3E-6	1.38	.55	.21	1H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00021.49	1H-70F-

06425 LUBE GREASE KRYTOX 21 GID: DBXXXX

MANF: DUPONT

....NO TEST DATA AVAILABLE....

06342 LUBE GREASE KRYTOX 240AB GID: DBEFXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1050		250	0.060	0	20
B	MECH	1050	72	250	0.060	0	20

00515 LUBE GREASE KRYTOX 240AC GID: DBEFXX

MANF: DUPONT

SPEC: MB0140-005 MB0150-005
MMS-N-425

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE
	N2O4
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	-297	0.050	0	160
B	PNEU	1000		200	0.060	00	20
B	PNEU	1000		250	0.063	0	20
B	PNEU	10000		130	0.060	0	20
B	PNEU	10000		200	0.060	0	20
B	MECH	10000	72	70	0.050	0	140
I	PNEU	10000		70	0.060	01	01
Z	MECH	11000	72	70	0.050	2	33
X	PNEU	1500		250	0.050	02	03
X	PNEU	1500		500	0.050	01	02
B	PNEU	1500		70	0.050	0	40
I	PNEU	2500		250	0.050	01	01
B	PNEU	2500		70	0.050	00	20
X	PNEU	2500		70	0.060	03	47

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005856 5

00515 LUBE GREASE KRYTOX 240AC (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	3000	72	-297	0.050	0	20
X	PNEU	3000		130	0.060	02	12
X	PNEU	3000		70	0.050	08	111
X	PNEU	3500		70	0.050	11	103
X	PNEU	3500		70	0.060	02	18
X	PNEU	4000		130	0.060	02	15
X	PNEU	4000		70	0.050	11	37
X	PNEU	4500		70	0.050	05	35
X	PNEU	4500		70	0.060	09	64
X	PNEU	4500		70	0.060	9	64
X	PNEU	5000		130	0.060	13	56
B	MECH	5000	72	70	0.050	0	39
X	PNEU	5000		70	0.050	5	31
X	PNEU	5000		70	0.060	13	56
X	PNEU	5500		130	0.060	03	12
B	MECH	5500	72	530	0.010	0	40
B	MECH	5500	72	530	0.050	0	10
X	PNEU	5500		530	0.050	02	02
B	MECH	5500	72	530	0.507	0	20
X	PNEU	5500		70	0.060	09	29
B	MECH	600	72	700	0.050	0	20
Z	MECH	6000	72	530	0.047	7	17
B	MECH	6000	72	70	0.050	0	42
X	PNEU	6000		70	0.050	03	08
X	PNEU	6000		70	0.060	08	30
X	PNEU	6500		130	0.060	02	07
X	PNEU	6500		70	0.060	07	33
B	MECH	7000	72	70	0.050	0	42
X	PNEU	7000		70	0.060	08	17
X	PNEU	7500		130	0.060	02	02
X	PNEU	7500		70	0.060	06	10
B	MECH	8000	72	70	0.050	0	18
X	PNEU	8000		70	0.060	01	05
X	PNEU	8500		70	0.060	02	04
B	MECH	9000	72	70	0.050	0	18
X	PNEU	9000		70	0.060	02	02
I	PNEU	9500		70	0.060	01	01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.20	.08	.00	SEE TEST REPORT

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00019.80	

60150 LUBE GREASE KRYTOX 240AD GID: DBXXXX

MANF: DUPONT

....NO TEST DATA AVAILABLE....

62555 LUBE GREASE KRYTOX 240AZ GID: CZCNXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		02.10	NONE
A	1	025.9	014.3	0.011	0.003		03.20	NONE
A	1	033.0	014.3	0.001	0.003		02.90	SMALL
A	1	033.0	014.3	0.011	0.003		00.90	NONE
A	1	100.0	019.0	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	40		70	0.001	0	20
B	MECH	40	72	70	0.001	00	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005857 7

62555 LUBE GREASE KRYTOX 240AZ (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.2E-6	38.90	9.24		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
V	00002.85	

20134 LUBE GREASE KRYTOX 250AB GID: DBEFXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1050	70	250	0.050	0	60
B	MECH	1050	72	250	0.050	0	20
X	PNEU	1050	70	250	0.060	8	71
B	PNEU	500		250	0.060	0	120
B	PNEU	500		250	0.060	0	99
B	PNEU	500		70	0.005	0	20
B	MECH	500	72	70	0.050	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
V	00017.48	

06179 LUBE GREASE KRYTOX 283AB GID: DBEFXX

MANF: DUPONT

....NO TEST DATA AVAILABLE....

85379 LUBE GREASE KRYTOX GPL103 GID: CZXXXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	415	72	-290	0.05	00	20

61213 LUBE GREASE MOLYCOTE C40 CHAIN GID: DBXXXX

MANF: LUBRI-KOTE CO INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.002	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.002	0.003	00.52	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	8.1E-6	90.97	.00		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00020.01	

65072 LUBE GREASE NYE 899 GID: DBBPXX

MANF: WILLIAM F NYE INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	10	-297	0.060	0	20

60815 LUBE GREASE OXY 8 GID: DBEFXX

MANF: FLUORAMICS INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.005	0.003		00.70	NONE
A	1	033.0	014.3	0.005	0.003		01.40	NONE

FSC

RT	FLUID NAME
A	N204

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	10000	72	70	0.003	0	40
B	MECH	1500	72	70	0.003	0	40
B	PNEU	5000		70	0.003	0	40
B	MECH	5000	72	70	0.003	0	21
X	PNEU	550		300	0.060	1	01
X	PNEU	5500		100	0.060	2	10
X	PNEU	5500		400	0.060	1	01

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005858 9

60815 LUBE GREASE OXY 8 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	5500		500	0.060	1	01
X	PNEU	5500		600	0.060	1	01
X	PNEU	5500		700	0.060	2	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	49.20	14.55		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00008.30	

20353 LUBE GREASE PETROLATUM/MOS2 GID: DBXXXX

MANF: SPEC: MIL-T-83483

....NO TEST DATA AVAILABLE....

65353 LUBE GREASE POLYMER MPG2 GID: DBXXXX

MANF: DUBOIS CHEMICALS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.7E-6	53.22	10.03	.29	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

65272 LUBE GREASE RHEOLUBE 738 GID: CZXXXX

MANF: WILLIAM F NYE INC SPEC: SP-R-0022A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	48.64	8.11	.14	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

06265 LUBE GREASE RYKON PREMIUM 2EP GID: DBXXXX

MANF: AMOCO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	6.0E-6	12.98	6.47		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

64315 LUBE GREASE SH340

MANF: TORAY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5				00.70	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 00022.12	

64060 LUBE GREASE SILICONE GID: DOCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.001		00.09	01.80	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 00022.28	

06110 LUBE GREASE SILICONE DC5 GID: DBCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005	0.003		02.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70	0.005	0	20
B	PNEU	1000		72	0.005	0	20
X	MECH	14.7	72	-297	0.005	04	04

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005859 0

06110 LUBE GREASE SILICONE DC5 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	1.01	.39		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00040.40	

05632 LUBE GREASE SILICONE DC971V GID: DBCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.010	0.005	00.16	09.60	NONE
X	1	023.8	014.5	0.010	0.005	00.07	12.00	T MOD
X	1	030.0	010.0	0.010	0.010	00.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.6E-6	.99	.30		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00022.72	

60318 LUBE GREASE SILICONE G683 GID: DBCKXX

MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.62	.07	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00011.25	

62329 LUBE GREASE SILICONE G9042 GID: DBCKXX

MANF: MCGHAN NUSIL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.05	.00	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

62330 LUBE GREASE SILICONE G9052 GID: DBCKXX

MANF: MCGHAN NUSIL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.05	.01	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

65188 LUBE GREASE SILICONE GE688 GID: DBCKXX

MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00001.50	

63492 LUBE GREASE SLICK 50 GID: DBXXXX

MANF: PETROLON INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.130		00.04	12.00	T NONE
C	1	025.9	014.3	0.130		02.14	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.3E-6	24.60	14.57	.70	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00021.88	

62395 LUBE GREASE STOPCOCK SILICONE GID: DBCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.043	0.010	00.40	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00021.72	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005860 7

60498 LUBE GREASE SUPERMIL ASU31052 GID: DBGGXX

MANF: AMOCO — SPEC: MIL-G-25013C

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		025.9	014.3					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00019.79	

00106 LUBE GREASE THERMAL DC340 HS GID: DBCKXX

MANF: DOW CORNING — SPEC: MB0110-005/T1 — MB0110-005T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010			04.00	NONE
A	1	030.0	010.0	0.010		0.003	00.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-7	.06	.00		48H-250F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

60735 LUBE GREASE THERMAL JOINT CPD GID: DBXXXX

MANF: THERMALLOY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00034.84	

60524 LUBE GREASE THERMOCOTE 250

MANF: THERMALLOY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.90	.22	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	V 00004.73	

61024 LUBE GREASE TRIBOLUBE 10 GID: DBXXXX

MANF: AEROSPACE LUBRICANTS — SPEC: MC-61024 — MIL-G-27617C

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	18.36	4.62	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00021.12	

60862 LUBE GREASE TRIBOLUBE 10C GID: DBXXXX

MANF: AEROSPACE LUBRICANTS — SPEC: MIL-G-27617CT3 — MIL-G-27617T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	MMH
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	10000		70	0.060	1	01
B	MECH	10000	72	72	0.055	0	60
B	PNEU	2000		70	0.060	0	40
X	PNEU	2500		70	0.060	2	22
X	PNEU	3000		70	0.060	4	28
X	PNEU	3570		70	0.060	4	42
X	PNEU	4000		70	0.060	5	47
X	PNEU	4500		70	0.060	2	14
X	PNEU	5000		70	0.060	3	05
X	PNEU	6000		70	0.060	2	04
X	PNEU	7000		70	0.060	1	01
X	PNEU	8000		70	0.060	1	01
X	PNEU	9000		70	0.060	1	01

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005861 9

65071 LUBE GREASE TRIBOLUBE 15 GID: DBXXXX
MANF: AEROSPACE LUBRICANTS SPEC: MIL-G-27617D

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	10	-297	0.060	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.06	.00	.01	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65477 LUBE GREASE TRIBOLUBE 15MS GID: DBXXXX
MANF: AEROSPACE LUBRICANTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.15	.03	.01	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65478 LUBE GREASE TRIBOLUBE 15RP GID: DBXXXX
MANF: AEROSPACE LUBRICANTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	615	72	-262	0.050	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.12	.01	.01	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65408 LUBE GREASE TRIBOLUBE 16 GID: DBXXXX
MANF: AEROSPACE LUBRICANTS SPEC: MIL-G-27617DT3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	10000	72	70	0.050	00	20
B	MECH	614.7	72	-290	0.050	0	20

85378 LUBE GREASE TRIBOLUBE 17C GID: DBXXXX
MANF: AEROSPACE LUBRICANTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	M	615	72	-256	0.05	00	20

80157 LUBE GREASE UNITEMP 500
MANF: TEXACO
....NO TEST DATA AVAILABLE....

05070 LUBE GREASE VERSILUBE G300 GID: DBXXXX
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.70	3.63	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64024 LUBE GREASE X5-8003 SILICONE GID: AYCKXX
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.15	.02		

ODOR

RT	RT WEIGHT	CURE
X	00022.87	

TOXICITY

64316 LUBE GREASE Y VAC 3
MANF: MONTEFLUOUS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5				01.10	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005862 0

64316 LUBE GREASE Y VAC 3 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00022.08	

TOXICITY

05329 LUBE LUBRICOID PHENOLIC/TFE GID: AHCNBX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.017		00.86	02.40	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.8E-7	1.64	.04		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05602 LUBE METAL/GLASS PS101 INORGANIC GID: CZXXXX

....NO TEST DATA AVAILABLE....

60129 LUBE MOS2 PETROLATUM

MANF: SPEC: MIL-T-5544 MIL-T-83483

....NO TEST DATA AVAILABLE....

05952 LUBE NASA PS101/C800 INORGANIC GID: CZXXXX

....NO TEST DATA AVAILABLE....

60124 LUBE O-RING

MANF: SPEC: STW5-2823

....NO TEST DATA AVAILABLE....

63292 LUBE OIL APIEZON C GID: DCXXXX

MANF: BIDDLE CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	81.19	47.47	.00	1H-150F-

ODOR

RT	RT	WEIGHT	CURE
	K	00005.00	

TOXICITY

20512 LUBE OIL CORR INHIBIT X90315 GID: DCEKXX

MANF: WILLIAM F NYE INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		01.80	NONE
A	1	033.0	014.3	0.001	0.003		01.40	NONE
B	1	100.0	020.2	0.001	0.003		07.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.4E-7	93.04	6.10		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.01	

TOXICITY

05370 LUBE OIL DC200 SILICONE GID: DCCKCK

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.010	0.010	00.55	12.00	T NONE
X	1	023.8	014.5	0.010	0.010	08.60	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.14	

TOXICITY

06423 LUBE OIL DC510 SILICONE GID: DCCKXX

MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.16	.13	.00	24H-125F-0psiaVACUUM

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005863 2

61343 LUBE OIL FLUOROLUBE FS-5 GID: DCEFXX
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00019.13	

63332 LUBE OIL FLUOROLUBE LG160 GID: DCXXXX
MANF: FISHER SCIENTIFIC
HOOKER CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	72	-220	0.050	0	20

61201 LUBE OIL FOMBLIN Y06 GID: DCBOXX
MANF: MONTEDISON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.010	0.010	00.01	00.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	PNEU	1000		150	0.050	0	04
B	MECH	10000	72	150	0.050	0	80
B	PNEU	10000		150	0.060	0	100
B	PNEU	10000		150	0.060	0	99
I	PNEU	5000		150	0.060	0	07
I	MECH	5015	72	150	0.050	0	15
I	PNEU	5015		150	0.060	0	06
I	PNEU	6000		150	0.060	0	08
I	PNEU	7000		150	0.060	0	13
I	PNEU	8000		150	0.060	0	09
I	PNEU	9000		150	0.060	0	07

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00020.46	

64942 LUBE OIL FOMBLIN Y140/13 GID: DCXXXX
....NO TEST DATA AVAILABLE....

60496 LUBE OIL FOMBLIN Y16 GID: DCBBXX
MANF: MONTEDISON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	10000	72	150	0.050	0	80
B	PNEU	10000		150	0.060	0	40
B	PNEU	3500		150	0.060	0	20
X	PNEU	4500		150	0.060	3	44
X	PNEU	5015		150	0.060	3	22
I	PNEU	5500		150	0.060	0	08
B	PNEU	6500		150	0.060	0	20
X	PNEU	7000		150	0.060	4	12
X	PNEU	7000		150	0.060	4	2
I	PNEU	8000		150	0.060	0	04

62346 LUBE OIL FRIQUIL V220 CELLUBE GID: DCXXXX
MANF: STAUFFER CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	150	72	70	0.050	0	20
I	MECH	5000	72	70	0.050	01	02

MSFC-HDBK-527 REV F 9999942 0005864 4

Information Handling Services, 2000

62824 LUBE OIL HALOCARBON 11-14 GID: DCXXXX

MANF: HALOCARBON PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	72	-297	0.050	0	40

60816 LUBE OIL HALOCARBON 11-21S GID: DCBDXX

MANF: HALOCARBON PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		150	0.060	1	20
X	PNEU	2000		150	0.055	4	39
X	PNEU	2500		150	0.055	3	39
X	PNEU	3000		150	0.060	4	25
B	PNEU	3500		150	0.055	0	20
X	PNEU	3500		150	0.060	1	20
B	PNEU	3500		70	0.060	0	20
X	PNEU	3750		150	0.055	1	01
B	MECH	400	72	-297	0.050	0	20
X	PNEU	4000		150	0.060	6	46
X	PNEU	4000		70	0.060	2	19
X	PNEU	4250		150	0.055	1	01
X	PNEU	4500		150	0.055	2	09
X	PNEU	5500		70	0.060	3	10
X	PNEU	6000		150	0.055	3	03
X	PNEU	7000		150	0.060	2	02
X	PNEU	7000		70	0.060	2	05
B	MECH	9250	72	150	0.055	0	20

65241 LUBE OIL HALOCARBON 6.3 GID: DCXXXX

MANF: HALOCARBON PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	48.12	6.35	48.15	

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	72	-297	0.060	0	20

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

60739 LUBE OIL HALOCARBON 80-114 GID: DCBDXX

MANF: HALOCARBON PRODUCTS

....NO TEST DATA AVAILABLE....

62137 LUBE OIL HALOCARBON MO-10 GID: DCBDXX

MANF: HALOCARBON PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	10000	72	70	0.050	01	60
X	PNEU	10000		70	0.060	1	01
B	PNEU	2500		70	0.060	0	20
X	PNEU	3000		70	0.060	2	40
X	PNEU	4000		70	0.060	1	20
B	PNEU	4500		70	0.060	0	20
X	PNEU	5000		70	0.060	4	10
X	PNEU	7000		70	0.060	2	04
X	PNEU	8000		70	0.060	2	03
X	PNEU	9000		70	0.060	2	03

MSFC-HDBK-527 REV F 9999942 0005865 6

Information Handling Services, 2000

60642 LUBE OIL HALOCARBON SERIES 27S GID: DCXXXX

MANF: HALOCARBON PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70	0.060	0	20
B	MECH	10000	72	70	0.050	0	20
B	MECH	14.7	72	70	0.050	0	20
X	PNEU	1500		70	0.060	3	42
X	PNEU	3000		70	0.060	1	24
X	PNEU	3500		70	0.060	3	18

60834 LUBE OIL HOUGHTO-SAFE 1055 GID: DCXXXX

MANF: E F HOUGHTON & CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		020.9	014.7					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	150	72	160	0.050	1	1
Z	MECH	200	72	160	0.050	1	1
Z	MECH	250	72	160	0.050	01	03
X	MECH	50	72	160	0.050	02	03

60835 LUBE OIL HOUGHTO-SAFE 1120 GID: DCXXXX

MANF: E F HOUGHTON & CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		020.9	014.7					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	250	72	160	0.050	0	20
B	PNEU	250		160	0.060	0	20

65531 LUBE OIL KILOPOISE GID: COXXXX

MANF: ROCOL LIMITED

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	2.500		01.80	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	56.37	11.88	.01	

ODOR

TOXICITY

RT	RT WEIGHT	CURE
A	00021.85	

00903 LUBE OIL KRYTOX 143AC GID: DCXXXX

MANF: DUPONT

SPEC: ST51F324

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYD
C	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	10000	72	130	0.050	0	02
B	MECH	10000	72	72	0.050	0	20
I	MECH	4000	72	130	0.050	0	2
I	MECH	5000	72	130	0.050	0	2
B	PNEU	5000		70	0.050	0	20
B	MECH	5000	72	72	0.050	0	20
X	PNEU	5500		70	0.060	3	32
I	MECH	6000	72	130	0.050	0	2
X	PNEU	6000		70	0.050	4	19
Z	MECH	6000	72	72	0.050	0	02
I	MECH	7000	72	130	0.050	0	2
I	MECH	7000	72	72	0.050	0	02
I	MECH	8000	72	130	0.050	0	2
I	MECH	8000	72	72	0.050	0	02
B	MECH	9000	72	72	0.050	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.00	.45	.00	240H-140F-0psiaVACUUM

ODOR

TOXICITY

RT	RT WEIGHT	CURE
No test data		

MSFC-HDBK-527 REV F ■ 9999942 0005866 8 ■

Information Handling Services, 2000

20233 LUBE OIL PRESERVATIVE GID: DCXXXX
MANF: AQM
SPEC: MIL-L-3150
....NO TEST DATA AVAILABLE....

62012 LUBE OIL QUAKER STATE 90 GID: DCXXXX
MANF: QUAKER STATE
SPEC: MIL-L-2105

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE
C	MMH
C	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05063 LUBE OIL SILICONE F6-1101 GID: DCCKXX
MANF: DOW CORNING
SPEC: MB0140-008

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.27	.00	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00004.55	

63291 LUBE OIL SRG 10 GID: DCXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00005.00	

06113 LUBE OIL SYNTHETIC (DIESTER) GID: DCXXXX
MANF:
SPEC: MIL-23699
....NO TEST DATA AVAILABLE....

05065 LUBE OIL SYNTHETIC BASE
MANF:
SPEC: MIL-L-7808
....NO TEST DATA AVAILABLE....

05062 LUBE OIL VERSILUBE F50 SILICONE GID: DCCKXX
MANF: GENERAL ELECTRIC
SPEC: MIL-S-81087

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.007	0.003	01.18	12.00	T MOD
X	2	030.0	010.0	0.010		00.09	12.00	T NONE
X	1	030.0	010.0	0.010		1.9	12.00	T NONE

FSC

RT	FLUID NAME
C	HYD
C	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	1500	72	70		0	20
X	PNEU	1500		70		02	08
X	PNEU	1500		70		2	08

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.96	5.51	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	22.19	

20133 LUBE OIL VISCASIL 10000 SILICONE GID: DCCKXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.010	0.010	00.25	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.01	

65161 LUBE OIL WD40/LEEDER 241K GID: DCXXXX
MANF: GENERAL DYNAMICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
S					

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005867 T

65156 LUBE OIL WD40/M6 SEE REPORT GID: DCXXXX
MANF: GENERAL DYNAMICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
S					

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60817 LUBE PARKER O-LUBE SILICONE GID: DBCKXX
MANF: PARKER SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.010	0.010	01.30	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.6E-6	53.52	12.15	.05	

ODOR

RT	RT WEIGHT	CURE
	A 00020.16	

TOXICITY

06524 LUBE RB-PREMIUM GID: DBXXXX
MANF: TEXACO OIL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.010	0.010		08.00	NONE
X	1	025.9	014.3	0.010	0.010	00.73	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.4E-6	19.28	11.87	.07	

ODOR

RT	RT WEIGHT	CURE
A	A 00020.14	

TOXICITY

63493 LUBE ROYCO 13D GID: CZXXXX
MANF: ROYAL INDUSTRIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.3E-6	2.40	.88	.05	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60720 LUBE SANDSTROM 9A GID: DAEJGF
MANF: SANDSTROM PRODUCTS SPEC: MIL-I-46010

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	X 00002.25	

TOXICITY

06310 LUBE SPERMAFOL 5200
....NO TEST DATA AVAILABLE....

60231 LUBE SUPER-O-LUBE GID: DBXXXX
MANF: PARKER SEAL
....NO TEST DATA AVAILABLE....

61303 LUBE SYNTON PAO 100 GID: DCEFXX
MANF: UNIROYAL SPEC: MIL-G-81322B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		100.0	020.2					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	A 00020.28	

TOXICITY

61422 LUBE TEFLON PTFE SPRAY GID: CZCNXX
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005868 1

20001 LUBE TFE FLUOROCARBON TELOMER GID: CZCNXX
MANF: MILLER STEPHENSON SPEC: MIL-L-60326
....NO TEST DATA AVAILABLE....

20249 LUBE WET 37987 GID: DFCBXX
MANF: BALL BROS RESEARCH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-7	4.50	2.33		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61782 MAGNET 2V PERMENDUR GID: DMMCMI
MANF: ALLEGHENY LUDLUM SPEC: MC284-0429

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70		0	20

80056 MAGNETIC CORE T12-125 GID: ERXXXX
MANF: TOHOKU KINZOKU

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.260		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
X	48.962	

TOXICITY

64293 MAGNETIC CORE T12-60

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.480		00.09	12.30	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
X	00046.72	

TOXICITY

20623 MAKEUP CHEEKCOLOR POWDER GID: EXXXXX
MANF: REVLON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
X	00019.09	

TOXICITY

65022 MARKER CABLE HT-TMS-CM GID: EHXXXX
MANF: RAYCHEM CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.47	.01	.42	

ODOR

RT	RT WEIGHT	CURE
A	00026.24	

TOXICITY

62817 MARKER ELECTROLYTE MSC4 GID: APXXXX
MANF: MARKING METHODS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	500	72	-297		0	20

61342 MARKER METALLIC NIJI GOLD GID: APXXXX
MANF: YASUTOMO & CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.2E-6	95.13	2.24	40.89	

ODOR

RT	RT WEIGHT	CURE
V	00005.39	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005869 3

60898 MARKER METALLIC NIJI GREEN GID: APXXXX
MANF: YASUTOMO & CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.5E-6	8.76	3.46	.42	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00000.54	

61341 MARKER METALLIC NIJI SILVER GID: APXXXX
MANF: YASUTOMO & CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.2E-6	99.99	2.52	44.32	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00002.18	

60899 MARKER METALLIC NIJI WHITE GID: APXXXX
MANF: YASUTOMO & CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.5E-6	5.17	.66	.32	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	3.254	

06550 MARKER SLEEVE KYNAR THERMOFIT GID: ENCTXX
MANF: RAYCHEM CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.30	.09	.25	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00005.06	

05180 MARKER SLEEVING HT-TMS KYNAR/VITON HS GID: ETCTDE
MANF: RAYCHEM CORP

SPEC: MA0150-059

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.012			02.00	NONE

FSC

RT	FLUID NAME
	No test data

RT-1800

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.42	.03		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

64118 MARKER STRIP NEMA GR XPC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.031		00.30	08.80	T SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00024.48	

20589 MARKING CRAYON 900 GRAPHITE BLK GID: AKEHXX
MANF: DIXON INDUSTRIES

SPEC: ST80C765-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.010		00.10	NONE
A	1	033.0	014.3	0.001	0.010		00.20	NONE
A	1	100.0	020.2	0.001	0.010		00.30	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.2E-5	.48	.00		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00009.04	

20588 MARKING CRAYON 900 YELLOW GID: AKXXXX
MANF: DIXON INDUSTRIES

SPEC: ST80C765-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.010		00.20	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005870 T

20588 MARKING CRAYON 900 YELLOW (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	033.0	014.3	0.001	0.010		00.50	NONE
A	1	100.0	020.2	0.001	0.010		00.70	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.2E-5	5.40	2.97		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00010.19	

20590 MARKING CRAYON 904 CARBON BLK GID: AKFOKK

MANF: DIXON INDUSTRIES SPEC: ST80C965-03

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.010		00.10	NONE
A	1	033.0	014.3	0.001	0.010		00.30	NONE
A	1	100.0	020.2	0.001	0.010		00.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-5	5.39	.26		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00010.02	

20654 MASCARA EVERY LAST LASH/BROWN GID: DDXXXX

MANF: HELENA RUBINSTEIN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00016.94	

20655 MASCARA EXTRA LNGTH WITH SEALER GID: DDXXXX

MANF: PRINCE MATCHABELLI

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00026.07	

20653 MASCARA LONG-NLUSH BLACK/BROWN GID: DDXXXX

MANF: NOXELL CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00023.76	

20656 MASCARA RICH LASH THICKENING GID: DDXXXX

MANF: ALMAY INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00013.15	

20621 MASCARA SUPER RICH GID: EXXXXX

MANF: REVLON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00023.04	

69971 MASK SOLDER PC401 CLEAR

MANF: CHEMLINE INDUSTRIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.0E-6	1.44	.00	.47	1H-70F- .5H-325F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005871 1

69972 MASK SOLDER PC401 GREEN

MANF: CHEMLINE INDUSTRIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.0E-6	2.77	.02	.42	1H-70F- .5H-325F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

69973 MASK SOLDER PC501 CLEAR

MANF: CHEMLINE INDUSTRIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.0E-6	4.59	.01	.53	1H-70F- .5H-305F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63947 MASK SOLDER PC501-GREEN GID: FKBGXX

MANF: CHEMLINE INDUSTRIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.7E-6	.51	.01	.33	.75H-275F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63399 MASKS DIVING NAVY RUBBER/PLAS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	100.0	100.0				00.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63939 MELAMINE WASHERS

MANF: SEASTROM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.030		00.26	01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00000.30	

TOXICITY

64812 MERCURY LAMP GID: EZAWXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
S	1	020.9	014.7				13.40	NONE
S	1	020.9	014.7			00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61502 MERLON M-50U POLYCARBONATE GID: DKCAXX

MANF: ROHM & HAAS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.239			00.30	NONE
A	1	030.0	008.0	0.237			01.10	NONE
I	1	040.0	008.0	0.237			06.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.6E-6	.15	.00		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.11	

TOXICITY

05420 MERLON M40 POLYCARBONATE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	25.9	14.3	0.120		00.02	9.25	LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005872 3

61366 METER SOUND LEVEL 2215 GID: FCXXXX

MANF: BRUEL & KJAER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	01009.92	

05659 MICA 495320/DFGC (INORG)

....NO TEST DATA AVAILABLE....

80119 MICRO-SWITCH 12TL1-1A GID: EZXXXX

MANF:

SPEC: MS27738-21A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3				00.25	NONE
A	1	025.9	014.3			00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61193 MICRO-SWITCH 12TL1-3 GID: BDXXXX

MANF: HONEYWELL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00093.54	

61194 MICRO-SWITCH 14TL1-3 GID: BDXXXX

MANF: HONEYWELL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00165.73	

60270 MICROFALLONS PHENOLIC

MANF: UNION CARBIDE

....NO TEST DATA AVAILABLE....

64025 MICROHEMATOCRIT TUBE HOLDER

MANF: DRUMMOND
SARSTEDT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00006.21	

61636 MICROPHONE HANDHELD PLUG/CABLE GID: FCXXXX

MANF: BENDIX
GLENAIR

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00244.15	

60813 MICROPHONE PREAMP 1400 GID: FCXXXX

MANF: RTS SYSTEMS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00917.68	

63184 MICROSWITCH WITH KEYS GID: FCXXXX

MANF: MICRO SWITCH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.3	1.560		00.02	10.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005873 5

05627 MILK OF MAGNESIA
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

60742 MINISWITCH M7-L-438 GID: FCXXXX
MANF: DIGITRAN

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	00031.76	

60682 MINISWITCHES GID: FCXXXX
MANF: DIGITRAN

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	00105.61	

20200 MOLD COMPOUND 514AG10D DAP GID: AZAQXX
MANF: AUGAT INC

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							X	00001.26	

06573 MOLD COMPOUND ABS

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	1.0E-6	1.13	.16	.00	.1H-399F-0psiaVACUUM	No test data			

63770 MOLD COMPOUND AKEMI #4 GID: AWXXXX
MANF: PLASTICS & TOOLING

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							X	00016.60	72H-70F-

05756 MOLD COMPOUND ALKD 2301 GLASS GID: AZIAXX
....NO TEST DATA AVAILABLE....

20137 MOLD COMPOUND ARITEMP 221 GID: AZXXXX
....NO TEST DATA AVAILABLE....

20260 MOLD COMPOUND BAKELITE GID: AZXXXX
MANF: UNION CARBIDE

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	1.0E-6	.63	.01	.00		No test data			

63431 MOLD COMPOUND BMC-15 6100 POLYES/GL GID: AZCBIA
MANF: PREMIX INC

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	1.5E-6	.56	.00	.18		A	A	00022.17	

60436 MOLD COMPOUND C2175 EPOXY GID: AZBGXX
MANF: FIBERITE SPEC: MC6346-01
....NO TEST DATA AVAILABLE....

20819 MOLD COMPOUND CELLU/ACETATE BUTYRAT GID: AZAWXX
MANF: HILLCOR

MSFC-HDBK-527 REV F 9999942 0005874 7

Information Handling Services, 2000

20819 MOLD COMPOUND CELLU/ACETATE BUTYRAT (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.061			09.00	MOD
X	1	025.9	014.3	0.061		00.20	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00019.92	

20201 MOLD COMPOUND DAP 514AGID YELLOW GID: AZAQXX

MANF: AUGAT INC

....NO TEST DATA AVAILABLE....

62118 MOLD COMPOUND DAP DC-62 GID: AZAQXX

MANF: COSMIC PLASTICS SPEC: GDI-30F MIL-M-146
MIL-P-19833

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.57	.02		.08H-300F- 24H-70F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

05030 MOLD COMPOUND DAP FS5 BLACK 8000 GID: AZAQAQ

MANF: ALLIED CHEMICAL SPEC: MIL-M-14F
PLASKON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.497			01.80	SMALL
X	1	030.0	010.0	0.130		00.10	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61239 MOLD COMPOUND DAP FS6 CAF BLUE GID: AZBYXX

MANF: ALLIED CHEMICAL SPEC: MIL-M-14

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.125		00.00	00.00	NONE
C	1	025.9	014.3	0.125		00.06	08.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.1E-5	.40	.00		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00020.46	

05196 MOLD COMPOUND DAP FS80/GLASS FILLED GID: AZAQIA

MANF: ALLIED CHEMICAL SPEC: GDI-30F MIL-M-14F
PLASKON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	009.0	0.140		00.02	08.00 T	NONE
I	2	030.0	010.0	0.133			00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.44	.00	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

63162 MOLD COMPOUND DAP GREEN GID: DKAQXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5				05.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61488 MOLD COMPOUND DAP SDG 6120 GID: AZBYXX

MANF: U S POLYMERIC

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005875 9

61488 MOLD COMPOUND DAP SDG 6120 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.090			00.10	NONE
C	1	023.8	014.5	0.090		00.07	06.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.24	

64873 MOLD COMPOUND DAP SDG 7717

MANF: THERMALLOY SPEC: MIL-M-14

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.120			02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	22.097	

05803 MOLD COMPOUND DAP/CARBON PROPRIETOR GID: AZFOXX

....NO TEST DATA AVAILABLE....

05069 MOLD COMPOUND DC302 SILICONE GID: DKCKXX

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

05369 MOLD COMPOUND DIAL 52-01 DAP GID: AZBYXX

MANF: ALLIED CHEMICAL
HITCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.500			00.70	NONE
C	1	030.0	010.0	0.088		00.10	12.00	T NONE
C	2	030.0	010.0	0.083			04.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.4E-6	.89	.02	.19	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00022.95	

61411 MOLD COMPOUND DUREZ 11844 BLK GID: AZXXXX

MANF: HOOKER CHEMICAL SPEC: MIL-F-14THFH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.060			01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

03047 MOLD COMPOUND DUREZ 11864 PHENOLIC GID: DLBXXX

MANF: HOOKER CHEMICAL SPEC: MIL-M-14FMFH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00009.20	24H-150F-

65195 MOLD COMPOUND E-21718/X49556 GID: AZXXXX

MANF: FIBERITE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	6.0E-6	.64	.01	.17	.5H-350F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
No test data		

65196 MOLD COMPOUND E-21718/X49560 GID: AZXXXX

MANF: FIBERITE SPEC: ASTM E 595-77

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005876 0

65196 MOLD COMPOUND E-21718/X49560 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	6.0E-6	.67	.02	.18	.5H-350F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05457 MOLD COMPOUND E-2748 EPOXY/GLASS GID: AZBGIA

MANF: FIBERITE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.064			03.10	SMALL
I	1	030.0	009.0	0.066		00.07	12.00	T SMALL
I	1	030.0	010.4	0.064		00.11	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.39	.00	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00156.62	

20536 MOLD COMPOUND E-3938C GLASS/EPOXY GID: AZBGIA

MANF: FIBERITE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.200		00.00	00.00	NONE
X	1	025.9	014.3	0.200		00.03	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.5E-6	.23	.00	.13	4H-350F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00020.01	4H-350F-

05977 MOLD COMPOUND EPIALL 1288BX GID: AZXXXX

MANF: ALLIED CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.8E-7	.39	.01		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.00	

05843 MOLD COMPOUND EPIALL 1908 GID: AZXXXX

MANF: ALLIED CHEMICAL

SPEC: ME414-0235

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.134		00.05	08.00	T NONE
A	1	025.9	014.3	0.259			01.30	NONE
A	1	030.0	009.0	0.255			02.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-6	.35	.02	.10	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.03	

20082 MOLD COMPOUND EPIALL 1914 EPOXY GID: AZXXXX

MANF: ALLIED CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.47	.00	.00	168H-70F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05393 MOLD COMPOUND EPIALL 1960 MNRI/EPOX GID: AZBGXX

MANF: ALLIED CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.75	.00	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

06597 MOLD COMPOUND EPIALL S-8723 EPOXY GID: AZBGXX

MANF: ALLIED CHEMICAL

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005877 2

06597 MOLD COMPOUND EPIALL S-8723 EPOXY (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.062			00.10	NONE
C	1	025.9	014.3	0.062		00.10	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.1E-6	1.04	.01	.20	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00020.80	

05664 MOLD COMPOUND EPOCAST 409-608 EPOXY GID: AZBGXX

MANF: FURANE

....NO TEST DATA AVAILABLE....

05938 MOLD COMPOUND EPOXY 2748 GID: AZBGXX

....NO TEST DATA AVAILABLE....

05852 MOLD COMPOUND EPOXY 403-53 GID: AZBGXX

....NO TEST DATA AVAILABLE....

05242 MOLD COMPOUND EPOXY EMC 480 GID: AZBMXX

MANF: MORTON CHEMICALS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.068			00.10	NONE
X	1	025.9	014.3	0.068		00.09	08.00	T MOD
X	1	030.0	009.0	0.129			02.80	MOD
X	1	033.0	014.3	0.068		00.12	08.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00020.13	

62083 MOLD COMPOUND EPOXY-DRY EPOX/POLYES

MANF: PERCY HARMS CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003	00.00	00.00	NONE
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.001		00.00	00.00	NONE
A	1	100.0	020.2	0.001			02.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	10000		70	0.001	0	20
I	MECH	10000	72	70	0.001	0	20
I	PNEU	2500		70	0.001	0	02
I	PNEU	4000		70	0.001	0	02
I	MECH	5000	72	70	0.001	0	2
I	PNEU	6000		70	0.001	0	02
I	PNEU	7000		70	0.001	0	02
I	MECH	7000	72	70	0.001	0	1
I	PNEU	8000		70	0.001	0	02
I	PNEU	9000		70	0.001	0	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00001.34	.5H-255F-

05585 MOLD COMPOUND EPOXY/GL/MIN 409-451 GID: AZBGGD

....NO TEST DATA AVAILABLE....

06483 MOLD COMPOUND EPOXY/GLASS FILLED GID: AZBGGD

MANF: SPEC: MIL-M-24325GEI

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005878 4

64825 MOLD COMPOUND ETHYLENE VINYL ACETAT GID: FCCUXX

MANF: PROTOTYPE & PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.252		00.02	01.60	T MOD
X	1	025.9	014.3	0.252		00.04	01.60	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.3E-6	.23	.02	.03	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00009.25	

61410 MOLD COMPOUND FIBERITE FM-8130 GID: AZBXIA

MANF: FIBERITE SPEC: MIL-M-14F

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.116			00.70	NONE
A	1	025.9	014.3	0.125			00.70	NONE
A	1	030.0	010.0	0.113			00.20	SMALL
A	1	033.0	014.3	0.116			03.70	NONE
A	1	033.0	014.3	0.125			01.20	NONE
X	2	100.0	019.0	0.113		00.03	06.00	T MOD
X	1	100.0	019.0	0.113		00.10	06.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.99	.02		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00020.36	

20212 MOLD COMPOUND FIBERITE FM4005 BLACK GID: AZAQXX

MANF: FIBERITE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.094		00.04	06.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.08	.02	.00	.08H-284F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00020.49	

60873 MOLD COMPOUND FIBERITE FM4008 GID: AZBGXX

MANF: FIBERITE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.063		00.03	12.00	NONE
A	1	025.9	014.3	0.125			00.39	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	2.2E-6	1.20	.00	.38	1H-350F- 2H-300F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	117.48	

02909 MOLD COMPOUND FIBERITE FM4030-190 GID: AZBXIA

MANF: FIBERITE SPEC: MIL-M-14F

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.2E-6	2.06	.05	.91	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.63	

00070 MOLD COMPOUND FS10 DAP GID: AZAQXX

MANF: ALLIED CHEMICAL SPEC: MIL-M-14FSDG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.125			00.90	SMALL
A	1	030.0	009.0	0.125			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005879 6

00070 MOLD COMPOUND FS10 DAP (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	033.0	014.3	0.125		00.02	07.60	SMALL

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.46	.03	.00	.66H-290F- 1H-275F-

ODOR

RT	RT	WEIGHT	CURE
	V	00020.30	.07H-290F- 1H-275F-

TOXICITY

80984 MOLD COMPOUND FS10 DAP TOX RATE STUDY

MANF: ALLIED CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00020.05	

TOXICITY

20503 MOLD COMPOUND GEON GID: AZXXXX

MANF: B F GOODRICH SPEC: ST90Y714-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3				00.20	NONE
X	1	025.9	014.3			36.30	03.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.6E-7	19.68	14.03		

ODOR

RT	RT	WEIGHT	CURE
A	A	00029.28	

TOXICITY

62537 MOLD COMPOUND GLASKYD 2051B GL/ALKD GID: AZAOIA

MANF: AMERICAN CYANAMID

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.062			01.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.3E-6	.99	.16	.11	

ODOR

RT	RT	WEIGHT	CURE
	X	00020.11	

TOXICITY

06558 MOLD COMPOUND GLASS FILL 7721-3PPS GID: AZGDXX

MANF: THERMALLOY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	1.00	.00	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

00763 MOLD COMPOUND M2840 MELAMINE GID: AZBYXX

MANF: FIBERITE SPEC: MIL-M-14FMMI-5

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.126			00.10	NONE
X	1	033.0	014.3	0.123		00.06	08.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.32	.01	.00	

ODOR

RT	RT	WEIGHT	CURE
	A	K 00019.90	

TOXICITY

05522 MOLD COMPOUND MACROLON 3000 GID: DKXXXX

MANF: PYROTRONICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.500			03.80	NONE
X	1	023.8	014.5	0.500			03.80	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	V 00024.97	

TOXICITY

MSFC-HDBK-527 REV F 9999942 0005880 2

Information Handling Services, 2000

05323 MOLD COMPOUND MARAGLASS 655/555 EPX GID: AZBGXX

MANF: ALLIED PRODUCTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.59	.00	.00	16H-180F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20215 MOLD COMPOUND MELAMINE/GLASS GF-5

MANF: POLYGON

....NO TEST DATA AVAILABLE....

06196 MOLD COMPOUND NORYL EN-265 GID: DKCHXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.065			00.30	SMALL
B	1	025.9	014.3	0.065			10.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-7	.11	.00		

ODOR

RT	RT WEIGHT	CURE
A	K 00020.06	

TOXICITY

20728 MOLD COMPOUND NORYL SE-1 GID: AZXXXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.075		00.12	06.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-7	.14	.00		

ODOR

RT	RT WEIGHT	CURE
A	V 00020.02	

TOXICITY

05791 MOLD COMPOUND NORYL SE-1-GFN3 30 GID: COIAXX

SPEC: GE TY SEI-GSN3

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.600			00.50	NONE
A	1	030.0	010.0	0.149			01.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH 65	72	250	0.254	0	20	

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.2E-6	.13	.00		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.18	

TOXICITY

05372 MOLD COMPOUND NYAFIL G10/40 GID: DLGSBD

MANF: DART INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.107		00.05	12.00 T	NONE
C	1	030.0	010.0	0.107			02.30	NONE
C	1	030.0	010.0	0.109		00.09	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	1.08	.02	.32	

ODOR

RT	RT WEIGHT	CURE
A	A 00020.02	

TOXICITY

06056 MOLD COMPOUND NYLATRON MOS2 FILLED GID: AZEJXX

MANF: DAYTON PRODUCTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	K 00023.30	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005881 4

60666 MOLD COMPOUND PLENCO 1512 ALKYD/GL GID: AZXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	009.0	0.063		00.08	07.20	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61465 MOLD COMPOUND PLENCO 1528 GID: AZCBXX

MANF: PLASTIC ENGINEERING SPEC: MIL-M-14F

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.132		00.00	00.00	NONE
A	1	033.0	014.3	0.132			02.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06259 MOLD COMPOUND PLENCO 1532 POLYESTER GID: AZCBXX

MANF: PLASTIC ENGINEERING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.550			00.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.14	

06574 MOLD COMPOUND POLY-ACETAL GID: AZXXXX

MANF: TOYOTA

....NO TEST DATA AVAILABLE....

06513 MOLD COMPOUND POLYES/GL G100 BMC-LS

MANF: PREMIX INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.125		00.00	00.00	NONE
A	1	030.0	010.0	0.131			01.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.42	

05755 MOLD COMPOUND POLYESTER GID: AZCDXX

MANF: FIBERLAY INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.075			02.40	SMALL
C	1	025.9	014.3	0.075		00.20	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.6E-6	1.35	.10	.21	8H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00020.36	8H-70F-

60276 MOLD COMPOUND POLYESTER MICA FILLED GID: AZXXXX

MANF: ISOCHEM RESINS

....NO TEST DATA AVAILABLE....

05262 MOLD COMPOUND POLYESTER/GLASS MAI-60 GID: AZCBGD

MANF: BUSSMAN SPEC: MIL-M-14

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.73	.04	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	19.6862	

05631 MOLD COMPOUND POLYETHYLENE GID: AZCCXX

MANF: EASTMAN KODAK

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005882 6

05631 MOLD COMPOUND POLYETHYLENE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.1E-6	.19	.05		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.00	

TOXICITY

06572 MOLD COMPOUND POLYETHYLENE GID: AZXXXX

MANF: TOYOTA

....NO TEST DATA AVAILABLE....

20887 MOLD COMPOUND POLYETHYLENE THERMAL ST

SPEC: ME416-0033

MANF:

....NO TEST DATA AVAILABLE....

20905 MOLD COMPOUND POLYPHENYLENE OXIDE GID: AZCHAD

SPEC: MIL-P-46129

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.100		00.20	07.20	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.11	.01	.00	

ODOR

RT	RT	WEIGHT	CURE
A	K	00010.46	

TOXICITY

20457 MOLD COMPOUND POLYPRO GID: AZXXXX

MANF: MONSANTO

....NO TEST DATA AVAILABLE....

61959 MOLD COMPOUND POLYSULFONE P-1720 GID: AZCIXX

SPEC: MIL-P-46120

MANF: UNION CARBIDE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.093			04.00	MOD
X	2	033.3	014.3	0.093			02.30	MOD
X	1	033.3	014.3	0.093			08.60	MOD
X	2	100.0	019.0	0.093		00.06	12.00	T MOD
X	1	100.0	019.0	0.093		00.19	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.06	

TOXICITY

20398 MOLD COMPOUND POLYURETHANE CASTABLE GID: CHCQXX

MANF: FLEXFORMERS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.126			02.10	MOD
X	2	033.0	014.3	0.126		00.04	12.00	T MOD
X	1	033.0	014.3	0.126		00.08	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.7E-6	.97	.38		

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.07	

TOXICITY

06260 MOLD COMPOUND POLYURETHANE NC101 GID: AZCQXX

....NO TEST DATA AVAILABLE....

20196 MOLD COMPOUND PROFAX 6527 POLYPROPYL GID: AZXXXX

MANF: BORG WARNER

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005883 8

62132 MOLD COMPOUND PROFAX 7231 GID: AZCGXX

MANF: HERCULES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-7	.36	.03		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62186 MOLD COMPOUND PROFAX SE-012 GID: AZBYXX

MANF: HERCULES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.073			03.00	MOD
X	1	025.9	014.3	0.073		00.07	05.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-7	.37	.09		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.14	

TOXICITY

20282 MOLD COMPOUND REXOLITE 1422 STYRENE GID: DLCMXX

MANF: OAK-ATLANTIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.135		00.01	00.90	NONE
X	1	025.9	014.3	0.135		00.09	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.14	.02	.00	24H-212F-

ODOR

RT	RT WEIGHT	CURE
	A 00020.14	

TOXICITY

65261 MOLD COMPOUND RX 3-1-530 GID: AZAQXX

MANF: ROGERS CORP SPEC: MIL-M-14

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3			0.04	06.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.4E-6	1.02	.05	.26	

ODOR

RT	RT WEIGHT	CURE
	V 108.4	

TOXICITY

62408 MOLD COMPOUND RYTON R-10 GID: ACFVXX

MANF: PHILLIPS CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.102			00.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.4E-6	.09	.00	.03	

ODOR

RT	RT WEIGHT	CURE
A	A 00053.12	

TOXICITY

06217 MOLD COMPOUND RYTON R-4 GID: DUCHXX

MANF: PHILLIPS CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.114			00.20	NONE
A	1	023.8	014.5	0.236			00.10	NONE
A	1	031.0	010.0	0.114			00.60	NONE
A	1	031.0	100.0	2.361			02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.18	.55	.00	

ODOR

RT	RT WEIGHT	CURE
A	V 00020.00	

TOXICITY

MSFC-HDBK-527 REV F 9999942 0005884 T

Information Handling Services, 2000

84228 MOLD COMPOUND RYTON R-5

MANF: PHILLIPS CHEMICAL

....NO TEST DATA AVAILABLE....

60712 MOLD COMPOUND RYTON R-6 GID: DUCHXX

MANF: PHILLIPS CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.245			00.10	NONE
A	1	031.0	010.0	0.245			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	6.1E-7	.07	.01		

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.00	

TOXICITY

62409 MOLD COMPOUND RYTON R-7 GID: ACFVXX

MANF: PHILLIPS CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.113			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.4E-6	.08	.01	.03	

ODOR

RT	RT	WEIGHT	CURE
A	A	00040.27	

TOXICITY

05866 MOLD COMPOUND S-8723 EPOXY GID: AZBGXX

MANF: PLASKON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.125		00.00	00.00	NONE
C	1	020.9	014.7	0.125		00.04	12.00	T SMALL
I	1	025.9	014.3	0.125		00.05	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.2E-6	.77	.01	.21	

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.22	

TOXICITY

65254 MOLD COMPOUND TA-88-50 GID: AZXXXX

MANF: T A MFG CORP SPEC: C-85052

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.067			00.50	NONE
X	1	025.9	014.3	0.067		00.05	05.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.17	.08		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.14	

TOXICITY

06560 MOLD COMPOUND TFE/GLASS/MOS2 GID: AZCNEJ

MANF: AQM

....NO TEST DATA AVAILABLE....

06140 MOLD COMPOUND TPX METHYLPENTENE GID: AZXXXX

....NO TEST DATA AVAILABLE....

62103 MOLD COMPOUND URETHANE VL422M2 GID: AZCQXX

MANF: VERNAY LABORATORIES SPEC: ST20P677-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.130		00.02	06.10	T MOD
X	1	025.9	014.3	0.130		00.11	06.10	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005885 1

62103 MOLD COMPOUND URETHANE VL422M2 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-6	8.47	1.42		

ODOR

RT	RT	WEIGHT	CURE
	V	00019.71	

TOXICITY

62185 MOLD COMPOUND VALOX 420 SEO GID: AZBYXX

MANF: AUGAT INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.071			00.10	NONE
C	1	023.8	014.5	0.071		00.58	05.90	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.6E-7	.19	.04		

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.15	

TOXICITY

62363 MOLD COMPOUND VISILOX V201 A/B SIL GID: AZCKXX

MANF: VISILOX SYSTEMS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.8E-6	1.64	.39	.03	2H-150F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05283 MOLD RELEASE AGENT TFE MS-122 GID: DACNXX

MANF: MILLER STEPHENSON SPEC: MIL-L-60326T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.001	0.003		01.20	NONE
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.001	0.003	00.00	00.00	NONE
A	1	100.0	020.2	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	10000	72	70	0.001	0	20
B	PNEU	10000		72	0.002	0	20
I	PNEU	7000		70	0.002	0	02
I	PNEU	8000		70	0.002	0	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	13.20	6.77	.00	

ODOR

RT	RT	WEIGHT	CURE
A	X	00001.73	168H-70F-
			24H-150F-

TOXICITY

64078 MOLDING COMPOUND NYLOMAR PL32L-25

MANF: MARSTON BENTLEY INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.001		00.20	01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.3E-6	1.71	.00	.50	

ODOR

RT	RT	WEIGHT	CURE
A	K	00011.64	

TOXICITY

85513 MOOG A22035 LUBRICANT

MANF: EVANS PRODUCTS SPEC: A22035 (BASIC)

....NO TEST DATA AVAILABLE....

20268 MOTOR ELECTRIC P/N 47A232920A GID: EZGTXX

MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00717.87	

TOXICITY

60648 MOTOR GLOBE

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005886 3

20241 MOTOR GLOBE 43A1578
MANF: GLOBE ALBANY CORP
....NO TEST DATA AVAILABLE....

60856 MOTOR P/N47A232920A S/N02
MANF: MAGNETICS
....NO TEST DATA AVAILABLE....

63190 MSA FOAM COATED WITH HYPALON NFR2200
MANF: GACO WESTERN INC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.125	0.125		03.20	SMALL	No test data	No test data						

63188 MSA-1/TURCO T6109 TOPCOAT GID: DDXXXX
MANF: TURCO PROD

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
I	1	020.9	014.7	0.375	0.125	00.07	12.0 T	NONE	No test data	No test data						
B	1	020.9	014.7	0.125	0.125		06.80	NONE								

63189 MSA/HYPALON NFR2200/ACTIVATOR
MANF: GACO WESTERN INC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.125	0.125		03.30	SMALL	No test data	No test data						

63146 MTA-2 GID: DDXXXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7	0.312	0.125		06.50	NONE	No test data	No test data						

63187 MULTI-LAYERED INSULATION 3M838 TEDLAR/NOMEX/KAPTON GID: CLCJBV

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7	0.040			08.00	MOD	No test data	No test data						

63439 MULTI-LAYERED INSULATION AL/AU COATED/VELCRO/ACRYLIC GID: CKXXXX
MANF: LOCKHEED SPEC: ST0370-001 ST0370-002

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.120		00.200	02.75	NONE	No test data	No test data						
A	1	020.9	014.7	0.110		00.190	05.00	NONE								

63521 MULTI-LAYERED INSULATION AL/FEP/DACRON/POLYMIDE GID; FJGDFJ
MANF: SCHULTZ CO
SHELDAHL

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.046		00.22	03.50	NONE	No test data	No test data						

65172 MULTI-LAYERED INSULATION AL/KAPTON/DACRON/NOMEX/MYLAR GID: CKCBBV
MANF: APEX SPEC: MIL-T-43636 MMS A569
MARTIN MARIETTA MMS Y985 MMS-J-690

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.050			01.40	NONE	No test data	No test data						

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005887 5

65172 MULTI-LAYERED INSULATION AL/KAPTON/DACRON/NOMEX/MYLAR (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.031		00.10	12.00	T NONE
A	1	020.9	014.7	0.040			01.00	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

63496 MULTI-LAYERED INSULATION AL/MYLAR/KEVLAR/DACRON GID: FJGDFJ
SPEC: MIL-T-87128
MANF: B F GOODRICH
SCHULTZ CO
SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.068		00.05	00.10	NONE
C	1	020.9	014.7	0.068		00.19	12.10	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62703 MULTI-LAYERED INSULATION ALUMINIZED FIBERGLASS/FEP TEFLON TAPE/SILVER/INCONEL/POLYESTER GID: CLBOFJ
SPEC: MB0125-064AT1C3
MB0135-034T1
MB0125-065T3C3
MB0135-062
MANF: ROCKWELL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.015		00.00	00.00	NONE
C	1	020.9	014.7	0.015		00.18	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63441 MULTI-LAYERED INSULATION ALUMINIZED KAPTON GDC GID: CKXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.035		01.00	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60780 MULTI-LAYERED INSULATION ALUMINIZED KAPTON/ALUMINIZED MYLAR/DACRON/NOMEX GID: FJCDCB
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.020			00.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63442 MULTI-LAYERED INSULATION ALUMINIZED KAPTON/Y966 GID: CKXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.020		00.43	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62435 MULTI-LAYERED INSULATION BLANKET GID: CLBOFJ
MANF: NAVAL RESEARCH LAB
ROCKWELL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.015			01.80	SMALL
B	1	020.9	014.7	0.049		00.09	10.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.61	.03	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63734 MULTI-LAYERED INSULATION BLANKET THERMAL GID: FJXXXX
MANF: HAMILTON STANDARD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.014		00.00	00.00	NONE
A	1	020.9	014.7	0.023		00.40	04.60	NONE
A	1	020.9	014.7	0.023		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005888 7

63734 MULTI-LAYERED INSULATION BLANKET THERMAL (cont)

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.035		00.19	02.30	NONE						
A	1	020.9	014.7	0.035		00.00	00.00	NONE						
A	1	020.9	014.7	0.026		00.00	00.00	NONE						
A	1	020.9	014.7	0.005		00.25	06.00	NONE						
I	1	020.9	014.7	0.019		01.21	12.10	T NONE						
A	1	020.9	014.7	0.019		00.00	00.00	NONE						
A	1	020.9	014.7	0.005		00.00	00.00	NONE						
A	1	020.9	014.7	0.022		00.09	00.06	NONE						
A	1	020.9	014.7	0.022		00.00	00.00	NONE						
A	1	020.9	014.7	0.021		00.00	00.00	NONE						
A	1	020.9	014.7	0.021		00.00	00.00	NONE						
I	1	020.9	014.7	0.025		01.30	12.10	T NONE						
A	1	020.9	014.7	0.025		00.00	00.00	NONE						
A	1	020.9	014.7	0.018		00.02	00.40	NONE						
A	1	020.9	014.7	0.018		00.00	00.00	NONE						
A	1	020.9	014.7	0.028		00.00	00.00	NONE						
I	1	020.9	014.7	0.168		00.04	05.80	T NONE						
A	1	025.9	014.3	0.015			01.00	NONE						

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.07	.01	.04	16H-140F-

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

61457 MULTI-LAYERED INSULATION DACRON NET B4A/ALUMINIZED KAPTON/PBI/ALUMINIZED KAPTON RIPSTOP GID: FJCBXX

MANF: ROCKWELL

SPEC: MB0135-042T2C1, MB0135-084T2C1, MB0135-083, SE-T-0092

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.030			01.10	SMALL	No test data	No test data				

61460 MULTI-LAYERED INSULATION DACRON NET B4A/GOLDIZED KAPTON/TG15000 SILICONE GLASS/G411660 GID: FJBVCD

MANF: ROCKWELL

SPEC: MB0135-038T2, MB0135-042, MB0135-041T5, MB0135-048T2

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.700			02.20	SMALL	No test data	No test data				

61458 MULTI-LAYERED INSULATION DACRON NET B4A/KAPTON/ALUMINUM/PBI GID: FJCBXX

MANF: ROCKWELL

SPEC: MB0135-042T2GA, MB0135-084T2GA, MB0135-083, SE-T-0092

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.030			02.10	NONE	No test data	No test data				

61456 MULTI-LAYERED INSULATION DACRON NET B4A/POLYBENZIMIDAZOLE/TG15000 SILICONE GLASS/TAPE G411970 ALUMINUM/KAPTON GID: FJCBXX

MANF: ROCKWELL

SPEC: MB0135-042/084, MB0135-084, MB0135-047T5, SE-T-0082

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.500			00.70	NONE	No test data	No test data				

61455 MULTI-LAYERED INSULATION DACRON NET B4A/TG15000 SILICONE GLASS/KAPTON/PBI GID: FJCBXX

MANF: ROCKWELL

SPEC: MB0135-042, MB0135-083, MB0135-047T5, MB0135-084T2C1

FLAMMABILITY									FSC	OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.500			02.00	NONE	No test data	No test data				

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005889 9

63443 MULTI-LAYERED INSULATION DACRON/MYLAR/ARMALON/TFE GID: CKXXXX

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.080	0.125	00.00	00.00	NONE	No test data		No test data						

63497 MULTI-LAYERED INSULATION FEP/GLASS/POLYIMIDE/KEVLAR GID: FJGDFJ
MANF: SHELDAHL SPEC: MIL-T-87128

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.032			04.30	SMALL	No test data		No test data						

63185 MULTI-LAYERED INSULATION GOLDIZED KAPTON GID: CKCDXX
MANF: ESA/ERNO

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	030.0	009.0	0.125			03.00	NONE	No test data		No test data						

60823 MULTI-LAYERED INSULATION GOLDIZED KAPTON/DACRON MESH/NOMEX GID: FJCDCB
MANF: MCDONNELL DOUGLAS SPEC: MB0135-038T2C1 MB0135-042
MB0135-048T2 MIL-T-43636T1

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.040			02.00	NONE	No test data		No test data						

64819 MULTI-LAYERED INSULATION GOLDIZED KAPTON/MYLAR GID: FJCDCC
MANF: ROCKWELL

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	2	023.8	014.5	0.035			00.10	NONE	No test data		No test data						
A	1	023.8	014.5	0.035			00.20	NONE									

64818 MULTI-LAYERED INSULATION GOLDIZED KAPTON/MYLAR/DACRON GID: FJCDCC
MANF: ROCKWELL

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	2	023.8	014.5	0.024			00.10	NONE	No test data		No test data						
A	1	023.8	014.5	0.024			00.20	NONE									

60784 MULTI-LAYERED INSULATION HITCO TG15000/G134600 GOLDIZED KAPTON GID: CKFVCD
MANF: HITCO SPEC: MB0135-047T4 MB0135-048T2
SHELDAHL

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.400			02.50	NONE	No test data		No test data						
A	1	020.9	014.7	0.410			02.60	NONE									

61493 MULTI-LAYERED INSULATION KAPTON AU OUTER KAPTON AL GID: FJCBXX
MANF: ROCKWELL

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.056			03.20	NONE	No test data		No test data						
A	1	025.9	014.3	0.057			03.90	NONE									

61550 MULTI-LAYERED INSULATION KAPTON/ALUMINUM/TG15000 SILICONE GLASS/DACRON NET B[illegible]/PBI GID: CLCDCB
MANF: ROCKWELL SPEC: MB0135-042 MB0135-047T5
MB0135-083

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.032		00.16	02.70	SMALL	No test data		No test data						

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005890 5

61550 MULTI-LAYERED INSULATION KAPTON/ALUMINUM/TG15000 SILICONE GLASS/DACRON NE[illegible]A/PBI (cont)

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	030.0	010.0	0.032		00.09	02.00	SMALL								

61869 MULTI-LAYERED INSULATION KAPTON/BETA GID: CKCDHL
MANF: ROCKWELL SPEC: MLO311-0010

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7	1.000			06.90	NONE	No test data	test data						

64978 MULTI-LAYERED INSULATION KAPTON/DACRON/A276 COATED GID: CKXXXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	020.9	014.7	0.030		18.00	12.00	T NONE	No test data	test data						

THERMAL VACUUM STABILITY					ODC	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	WEIGHT	CURE
S	5.0E-5					F[illegible]st data	

63495 MULTI-LAYERED INSULATION KAPTON/DACRON/BETA COVERED GID: CKXXXX
MANF: SEE TEST REPORT

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.030		00.13	01.30	NONE	No test data	test data						
A	1	020.9	014.7	0.003		00.00	00.00	NONE								
A	1	020.9	014.7	0.003		00.57	05.10	SMALL								

60792 MULTI-LAYERED INSULATION KAPTON/MYLAR/DACRON NET GID: FJCDCC
MANF: GENERAL ELECTRIC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	020.9	014.7	0.016		01.09	12.00	T NONE	No test data	est data						
X	1	020.9	014.7	0.070		00.75	12.00	T MOD								

THERMAL VACUUM STABILITY					OD	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	F	WEIGHT	CURE
A	1.0E-6	.44	.00	.00		t.	t data	

64838 MULTI-LAYERED INSULATION KAPTON/MYLAR/SILVER FOIL GID: FJXXXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	EST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	020.9	014.7	0.01[illegible]		00.09	12.00	T NONE	No test data	est data						

61659 MULTI-LAYERED INSULATION KAPTON/NOMEX/AU/TG 15000 GID: CKCDIA
MANF: ROCKWELL SPEC: V070-060068 V762-363817
SEE TEST NO.18471

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	EST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.750			04.00	NONE	No test data	est data						

62271 MULTI-LAYERED INSULATION MYLAR/ALUMINUM GID: FJFKXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	EST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	020.9	014.7	0.008		00.04	12.00	T MOD	No test data	est data						
X	1	020.9	014.7	0.008		00.30	12.00	T MOD								

63440 MULTI-LAYERED INSULATION PLASTIC/VELCRO/AU COATED GID: CKXXXX
MANF: LOCKHEED SPEC: ST0370-003 ST0370-004

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005891 7

63440 MULTI-LAYERED INSULATION PLASTIC/VELCRO/AU COATED (cont)

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7	0.010		00.20	08.50	NONE	No test data	No test data							

60678 MULTI-LAYERED INSULATION POLYURETHANE FOAM 416/SUPER KOROPON/RTV 560/HYPALON GID: FJCQBG
MANF: GENERAL PLASTICS SPEC: MAO608-303 MBO130-128T1

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	021.0	014.7	0.500		00.17	06.80	NONE	No test data	No test data							
B	1	023.8	014.5	0.500		00.19	10.00	NONE									

65047 MULTI-LAYERED INSULATION RADIATION SHIELD GID: EXXXXX
MANF: GDSS
SHELDAHL

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.010			02.20	NONE	No test data	B	MECH	50	72	70	0.007	00	20
B	2	020.9	014.7	0.002		00.00	00.00	NONE		X	MECH	50	15	70	0.050	00	20
B	1	020.9	014.7	0.002			08.20	NONE									

65252 MULTI-LAYERED INSULATION RADIATION SHIELD TEFLON GID: CKXXXX
MANF: GENERAL DYNAMICS SPEC: MIL-T-87128
SHELDAHL

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.010			02.00	NONE	No test data	No test data							

65344 MULTI-LAYERED INSULATION SLD BLANKETS NON STD TEST GID: CKXXXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.040			00.60	NONE	No test data	No test data							
X	1	020.9	014.7	0.040			05.40	MOD									

64864 MULTI-LAYERED INSULATION TEDLAR/ALUMINIZED MYLAR GID: CKXXXX
MANF: DUPONT SPEC: PMIC-SPEC-4223 PMIC-SPEC-4224

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7			00.15	12.00	T MOD	No test data	No test data							

64863 MULTI-LAYERED INSULATION TEDLAR/MYLAR/3M838/VELCRO GID: CKXXXX
MANF: VELCRO CORP SPEC: MIL-F-21F40

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	020.9	014.7			00.24	12.00	T SMALL	No test data	No test data							

64158 MULTI-LAYERED INSULATION TEDLAR/MYLAR/VELCRO #65 GID: CKXXXX
MANF: DUPONT SPEC: MIL-F-21840
VELCRO CORP

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	2	020.9	014.7			00.21	07.25	NONE	No test data	No test data							

63186 MULTI-LAYERED INSULATION TEDLAR/NOMEX/KAPTON GID: FJCJBV

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7	0.030			06.00	NONE	No test data	No test data							

MSFC-HDBK-527 REV F 9999942 0005892 9

Information Handling Services, 2000

64830 MULTI-LAYERED INSULATION TFE/DACRON/AL/MYLAR/NOMEX GID: CLBVFV

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.123			02.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64829 MULTI-LAYERED INSULATION TFE/DACRON/AL/MYLAR/POLYESTER GID: CLBVFV

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.119		00.00	00.00	NONE
C	1	020.9	014.7	0.119		00.08	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65263 MULTI-LAYERED INSULATION VELCRO/POLYESTER GID: CKBNCB

MANF: VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7				02.00	NONE
X	1	020.9	014.7			00.15	07.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60454 MULTI-LAYERED INSULATION VT70-060065 AL/POLYIMIDE GID: CLFJCD

MANF: ROCKWELL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025			02.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65057 MULTI-LAYERED TFE TAPE/CLAMP

MANF: BENDIX
MOXNESS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3				00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60811 NALGENE MA 255 TYPE 4 GID: AWGSXX

MANF: NALGENE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.013	0.003		03.30	NONE
A	1	030.0	009.0	0.014	0.003		03.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00008.44	.5H-70F-

64448 NAMEPLATES SSME GID: DDXXXX

MANF: NELSON NAMEPLATE CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20517 HOSECLIP P/N 85103531 GID: EXBVCK

MANF: CARDIO PULMONARY INSTRUMENTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.087		00.28	02.30	T MOD
X	1	100.0	014.3	0.087		01.20	02.30	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00009.70	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005893 0

63147 NYLAFIL G-12/40 GID: FCXXXX
MANF: WILSON FIBERFIL

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
I	1	020.9	014.7	0.123		00.01	05.00	T SMALL	No test data		No test data					
I	1	020.9	014.7	0.240		00.02	08.00	T SMALL								

05338 NYLATRON GS/GLASS FILLED NYLON GID: DKBSEJ
MANF: FIBRE MATERIAL CORP
POLYMER DEVELOPMENT

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	030.0	010.0	0.025			12.00	T MOD	No test data		No test data					
X	2	030.0	010.0	0.026		00.10	12.00	T LARGE								

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	WEIGHT	CURE
C	2.0E-6	2.77	.02	.65		A	00022.40	

63148 NYLATRON MOS2 FILLED NYLON GID: DUBSFW
MANF: POLYMER CORP

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	024.5	014.5	0.187		00.03	06.00	T MOD	No test data		No test data					

61114 NYLON 12 GID: DUBSXX
MANF: DUPONT

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	0.070		00.07	10.00	T MOD	No test data		No test data					
I	1	023.8	014.5	0.002		01.30	09.90	T NONE								
B	1	023.8	014.5	0.006		00.49	07.10	SMALL								

80169 NYLON 2257 ALUM-INIZED NEOPRENE COATED WITH 2310 NEOPRENE BIAS TAPE AND N- NEOPRENE ADHESIVE
MANF: TECHNICAL COATED FABRICS

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
B	2	020.9	014.7	0.012			00.10	NONE	No test data		No test data					
B	1	020.9	014.7	0.012		0.7	08.70	NONE								

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	WEIGHT	CURE
No test data						A	22.207	

63005 NYLON 6 MOC GID: DKBTXX

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.005			03.80	SMALL	No test data		No test data					

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	WEIGHT	CURE
B	1.0E-6	.85	.01	.00	24H-257F-	No test data		

05298 NYLON 6/6 GID: DUBTBT
MANF: BALLY RIBBON MILLS SPEC: MIL-M-20693 MIL-T-5608 CET4
CADILLAC PLASTICS
CHEMPLAST
KAUFMAN GLASS CO
MOLDEX
MONSANTO

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005894 2

05298 NYLON 6/6 (cont)

MANF: PORT PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	015.0	0.032			02.75	MOD
A	1	020.9	014.7	0.028			02.00	NONE
X	2	020.9	014.7	0.142		00.00	00.10	NONE
X	1	020.9	014.7	0.142		00.10	12.00	T LARGE
X	2	020.9	014.7	0.105		00.00	00.00	NONE
X	1	020.9	014.7	0.105		00.10	12.00	T LARGE
X	2	025.9	014.3	0.627			02.00	MOD
X	1	025.9	014.3	0.627		00.01	10.00	T MOD
X	1	025.9	014.3	0.400		00.01	06.00	MOD
B	2	025.9	014.3	0.028			00.30	NONE
B	1	025.9	014.3	0.028		00.09	11.20	NONE
X	1	030.0	010.0	0.080		00.10	12.00	T MOD

FSC

RT	FLUID NAME
C	N204

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		150	0.074	6	26
X	PNEU	1000		70	0.063	01	20
Z	MECH	1050	65	120	0.061	02	08
C	MECH	1250	55	150	0.076	0	20
X	PNEU	1250		150	0.077	2	02
B	PNEU	250		150	0.074	0	20
X	PNEU	500		150	0.075	2	14

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.21	.05	.00	

ODOR

RT	RT	WEIGHT
A	A	00020.22

TOXICITY

CURE

05910 NYLON 6/6 30% GLASS RF-1006 GID: DUBTGD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.81	.04	.00	

ODOR

RT RT WEIGHT

No test data

TOXICITY

CURE

06644 NYLON 6/6 ZYTEL 101 GID: AZBSXX

MANF: DUPONT

SPEC: ME171-0005-0001, ME171-0005-0003, ME171-0005-0004, ME171-0005-0005, ME171-0005-0007, ME171-0005-0008, ME171-0005-0009, ST62N 745/ILC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.062		00.06	12.00	T MOD
X	1	023.8	014.5	0.063		00.05	12.00	T MOD
X	1	025.9	014.3	0.128		00.04	12.00	T MOD
X	2	025.9	014.3	0.126		00.10	11.10	NONE
X	1	025.9	014.3	0.126		00.03	12.10	MOD
X	2	030.0	010.0	0.010		00.14	12.00	T MOD
X	1	030.0	010.0	0.010		00.42	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.031	2	03
B	MECH	1050	72	120	0.057	1	60
X	PNEU	2000		70	0.031	2	02
X	PNEU	3000		70	0.031	2	02
X	PNEU	500		70	0.031	2	13
X	PNEU	500		70	0.031	2	3

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.2E-7	1.13	.00		

ODOR

RT	RT	WEIGHT
A	A	00022.37

TOXICITY

CURE

05873 NYLON GLASS FILLED NY-029-S

....NO TEST DATA AVAILABLE....

05531 NYLON NITEX HC3-20 MONOFILAMEN GID: BFXXXX

MANF: TETKO INC

....NO TEST DATA AVAILABLE....

60257 NYLON ORANGE

MANF:

SPEC: MIL-C-8021

....NO TEST DATA AVAILABLE....

00019 NYLON PLASTIC GID: DUBTXX

MANF: MOLDEX

SPEC: MIL-P-17091

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		150	.079	3	04

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005895 4

00019 NYLON PLASTIC (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		150	0.079	3	4
X	PNEU	1250		150	.079	3	03
X	PNEU	1250		150	0.079	3	3
X	MECH	1250	65	150	0.079	0	20
B	PNEU	250		150	.075	0	20
B	PNEU	250		150	0.075	0	20
X	PNEU	500		150	.075	2	29
X	PNEU	500		150	0.075	2	29

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.13	.00	.00	72H-124F-

ODOR

RT
No test data

TOXICITY

RT	RT	WEIGHT	CURE

06003 NYLON/15% GLASS GID: DKBSIA
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.118			02.30	NONE
X	1	030.0	010.0	0.118		00.09	12.00	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.0E-6	.95	.02	.22	

ODOR

RT
A

TOXICITY

RT	RT	WEIGHT	CURE
	K	22.30	

64333 O-RINGS SPARE FOR FES FURNACE GID: CHXXXX
MANF: NASA/MSFC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	K	00027.20	

64198 OAK BOARD COATED WITH KPR GID: COXXXX
MANF: OAK INDUSTRIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	K	00037.33	

64182 OAK BOARD UNCOATED
MANF: ROGERS CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	A	00038.11	

63893 OINTMENT POLYSPORIN ANTIBIOTIC GID: AWXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	X	00011.00	

61257 OINTMENT VASELINE CONSTANT CARE
....NO TEST DATA AVAILABLE....

64800 ORBITAL MAP AND COVER GID: DOGMCN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.086		00.47	09.90	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005896 6

61421 ORBITER RADIATOR COVER GID: FDXXXX

MANF: ROCKWELL

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.000	0.020		01.80	NONE	No test data	No test data							

63015 P-GASKET BMS 1-59 SILICONE GID: CHDPXX

MANF: SPEC: SE5549U

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	023.8	014.5	0.250			06.60	NONE	No test data	No test data							

62473 PACKAGE FOOD SARAN/POLYETHYLEN GID: DKCCBY

MANF: GENERAL ELECTRIC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	1.700		00.11	04.10	T MOD	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							X	00031.46	

64009 PACKAGING MATERIAL RUBBERIZED HAIR GID: DDHDXX

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							X	00022.35	

05675 PAD ATTENUATION HFT 3/16 4.0 GID: FJBXBV

MANF: HEXCEL

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	4.000		00.00	00.00	NONE	No test data	No test data							

63892 PAD PREP PROVIDINE-IODINE GID: EXXXXX

MANF: PRO DISPOSABLES

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							X	00004.17	

63150 PAD SILICONE GID: DHDPXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	030.0	009.0	0.200			02.50	NONE	No test data	No test data							

05539 PALLADIUM OXIDE (INORG)

....NO TEST DATA AVAILABLE....

64810 PANEL GL HONEYCOMB GID: BBHMFV

MANF: ROCKWELL

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.500			00.50	NONE	No test data	No test data							

60475 PANEL HONEYCOMB/COATING CTL 15 GID: FDHMXX

MANF: HUGHES AIRCRAFT SPEC: HMS 15-1099

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.500			00.10	SMALL	No test data	No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005897 8

05808 PANEL LEXAN 934111 EDGELIGHTED
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

64108 PANELS AL PAINTED W136231 GID: EXXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.250		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00397.32	

05710 PAPER 414 NOMEX GID: DIBVXX
MANF: DUPONT SPEC: MIL-I-24204

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.012			01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00018.97	

63151 PAPER ARTIST 240-5/FASSON 824 GID: DIXXXX
MANF: STRATHMORE PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	024.5	014.5	0.071			00.20	NONE
C	1	024.5	014.5	0.071		00.71	12.00	T NONE
I	1	030.0	010.0	0.071		00.43	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00092.48	

63877 PAPER BOND HIGH RAG CONTENT GID: DIXXXX
MANF: GSA

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00008.62	

61173 PAPER CHART TYPE 58340 GID: DIXXXX
MANF: GOULD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	01680.40	

64113 PAPER COATED GID: DIXXXY
MANF: SOLOPAK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00006.12	

64276 PAPER COLORPHAST PH #9582 GID: DIXXXX
MANF: MCB REAGENTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00054.33	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005898 T

20117 PAPER COPACO GID: DIXXXX
MANF: ESSEX CHEM CORP
SPEC: MIL-I-695TR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.010		00.03	12.00	T NONE
C	1	023.8	014.5	0.010		00.78	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.15	

62338 PAPER DRY SILVER 7772 GID: DIAGXX
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00020.16	

62048 PAPER DRY-SILVER TYPE 7771 GID: DIGMMR
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.003		03.92	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00005.13	

63867 PAPER E-20 GID: EXXXXX
MANF:
SPEC: SF-88T-0

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00028.20	

63868 PAPER E-20 WITH PPC TONER SF-88T GID: DIXXXX
MANF: SHARP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00028.21	

60825 PAPER ELECTROGRAPHIC 45R11 GID: DIAUXX
MANF: VERSATEC INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.003		00.19	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00004.12	

06446 PAPER ERZ POLYETH/FC4101 COATED
....NO TEST DATA AVAILABLE....

60700 PAPER ESP-14 GID: DIXXXX
MANF: NICOLET PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	009.0	0.003		03.33	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00008.89	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005899 1

64449 PAPER FIBERFRAX GID: DIXXXX
MANF: DUPONT SPEC: RB0130-019

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20243 PAPER FILTER GID: DIXXXX
MANF: AQM
!...NO TEST DATA AVAILABLE....

80140 PAPER FILTER WHATMAN #1 GID: DIXXXX
MANF: WHATMAN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	22.41	

TOXICITY

80141 PAPER FILTER WHATMAN #42 GID: DIXXXX
MANF: WHATMAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	032.0	010.0	0.008		0.2	12.00 T	NONE
X	1	032.0	010.0	0.008		2.0	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	4.28	.00	3.66	

ODOR

RT	RT	WEIGHT	CURE
A	K	22.386	

TOXICITY

62277 PAPER FITCHBURG TIME MARK 30 GID: DIXXXX
MANF: LITTON INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.004		02.64	11.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00019.03	

TOXICITY

06427 PAPER FREEZER WRAP POLYETH COATED GID: DIXXXX
MANF: H P SMITH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.004		00.09	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80167 PAPER GRAPHICS CONTROL ELECTROSTATIC COPY P/N 4036R WITH VERSATEC TYPE H/V80 TONER GID: DIXXXX
MANF: SCHERER LABORATORIES SPEC: FSN 7530-01-1077383

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.004		0.3	12.00 T	NONE
X	1	030.0	010.0	0.004		3.2	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	22.009	

TOXICITY

65362 PAPER HP INKJET 92261M GID: DIXXXX
MANF: HEWLETT-PACKARD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00018.05	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005900 4

80256 PAPER INDEX LONG GRAIN PULP WOOD FIBER MATERIAL GID: DIXXXX
MANF:
SPEC: FSN 9310-00-0005027 FSN 9310-00-0005028
FSN 9310-00-0005030 UU-P-258

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	22.198	

TOXICITY

06021 PAPER JCP K-10 GID: DIXXXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.009		00.08	10.90	SMALL
C	1	025.9	014.3	0.009		01.23	10.90	T NONE
X	1	030.0	010.0	0.060			06.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00020.39	

TOXICITY

06020 PAPER JCP K-20 GID: DIXXXX
....NO TEST DATA AVAILABLE....

20581 PAPER KLEENEX TISSUE PACK GID: DIXXXX
MANF: KIMBERLY CLARK CORP
SPEC: ST10P827-01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00014.76	

TOXICITY

20269 PAPER KRAFT
....NO TEST DATA AVAILABLE....

20760 PAPER LINT FREE
....NO TEST DATA AVAILABLE....

60753 PAPER MAPS JCP E-20 GID: DIXXXX
MANF: EDWARD AFB

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00013.13	

TOXICITY

61529 PAPER NOMEX TYPE 410/ARAMID GID: BFBVXX
MANF: DUPONT
SPEC: MIL-I-24204

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002			03.50	NONE
A	1	023.8	014.5	0.003			04.90	NONE
X	1	030.0	010.0	0.010		00.03	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.2E-6	3.67	.00		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63152 PAPER NOMEX/HONEYCOMB GID: DJBVHM
MANF: ESA/ERNO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.265			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.16	.07	.00	2.5H-250F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005901 6

63152 PAPER NOMEX/HONEYCOMB (cont)

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
					144H-46F-			

60312 PAPER ONION SKIN GID: DIXXXX
MANF: SPEC: MIL-P-157
....NO TEST DATA AVAILABLE....

63153 PAPER PERVEL LH8613 GID: DIXXXX
MANF: PERVEL INDUSTRIES

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7	0.003		01.65	09.00	NONE	No test data		No test data							

60970 PAPER PHOTO 74 RC EKTACOLOR GID: DICBXX
MANF: EASTMAN KODAK

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	2	025.9	014.3	0.009		00.04	10.00	T SMALL	No test data		No test data							
B	1	025.9	014.3	0.009		00.78	10.00	T SMALL										

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data						A	V 00020.09	

80255 PAPER PHOTO 78 PLUS F COLOR PRINT MATERIAL GID: BSXXXX
MANF: EASTMAN KODAK

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	030.0	010.0	0.010		00.15	12.00	T SMALL	No test data		No test data							
C	1	030.0	010.0	0.010		01.30	12.00	T SMALL										

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data						A	K 22.305	

60966 PAPER PHOTO CIBACROME GID: DIAJXX
MANF: CIBA-GEIGY

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	025.9	014.3	0.010			01.50	SMALL	No test data		No test data							
C	1	025.9	014.3	0.010		00.83	12.00	T SMALL										

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data						A	A 00020.08	

20735 PAPER PHOTOGRAPHIC
....NO TEST DATA AVAILABLE....

65380 PAPER SCOTT #60 GID: DIXXXX
MANF: SCOTT PAPER CO

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	2	030.0				00.20	11.00	T NONE	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data						A	K 00022.48	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005902 8

60492 PAPER STICKY-BACK WHITE GID: DIXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	025.9	014.3	0.005	0.003	00.00	00.00	NONE
I	2	025.9	014.3	0.008		00.08	10.50	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.21	

80176 PAPER STRATHMORE SHEETS 100% COTTON FIBER SERIES 500 WHITE POSTERBOARD GID: DIXXXX

MANF: STRATHMORE PAPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.015		00.09	12.00	T NONE
C	1	030.0	010.0	0.015		0.8	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	21.857	

62276 PAPER TELETYPE PRINTER GID: DIXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	009.0	0.005		04.00	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62290 PAPER TELETYPEWRITER CARBON GID: DIFOXX

MANF: CELLU-PAK CONVERTERS SPEC: GS-005-70845

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.004		05.90	12.00	T NONE
I	1	030.0	009.0	0.004		05.64	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00007.79	

60618 PAPER TYVEK GID: DIXXXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.006		00.30	10.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.2E-6	.38	.06	.03	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00020.77	

61733 PAPER TYVEK STYLE 1073D GID: DTGMCE

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.007		00.30	11.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00004.53	

65111 PAPER XEROX 4200 GID: DIXXXX

MANF: XEROX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	025.9	014.3	0.004		00.20	11.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005903 T

65111 PAPER XEROX 4200 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00021.48	

20027 PARAFFIN WAX GID: DHXXXX
MANF: AQM
....NO TEST DATA AVAILABLE....

60427 PASTE 97% GOLD ELECTRICAL COND
MANF: SIMMONDS
....NO TEST DATA AVAILABLE....

62821 PASTE SILVER SOLDER GID: FKXXXX
MANF: FUSION INC SPEC: STL-1000-650

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	10000	72	68	0.050	4	21
B	MECH	9500	72	64	0.050	0	20

85335 PASTIC CELCON MC90
MANF: CELANESE
....NO TEST DATA AVAILABLE....

65298 PCB CONNECTOR/VALOX 420/RYTON
MANF: GENERAL ELECTRIC
HUGHES AIRCRAFT
PHILLIPS CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.600			01.50	NONE
A	1	030.0	010.0	0.600			01.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00032.72	

06497 PELLETHANE 2103 POLYETHER TUBE GID: EJBYXX
MANF: PLASTIC ENGINEERING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.062		00.14	12.00	T MOD
X	1	025.9	014.3	0.062		00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.8E-6	.91	.09	.43	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00019.74	

20740 PEN AG-7 BLK MED POINT ANTI-G GID: FCXXXX
MANF: FISHER PEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.375		00.00	00.00	NONE
A	1	030.0	009.0	0.375		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00022.87	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005904 1

63860 PEN BEROL POROUS TIP/INK 7722 GID: FCXXXX
MANF: BEROL CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							B	00000.02	1H-212F-

60664 PEN BIC F39 BLACK GID: FCXXXX
MANF: BIC INC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							X	00000.86	

64261 PEN BIC FS11 GID: FCXXXX
MANF: BIC INC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							X	00000.05	78H-70F-

60591 PEN CROSS 3504/REFILL 8543 GID: APXXXX
MANF: A T CROSS CO

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	00018.32	

60903 PEN EXPRESSO 2901/2902M RED GID: EXXXXX
MANF: SANFORD CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	00018.61	

80135 PEN FELT TIP BEIGE GID: APXXXX
MANF: SKILCRAFT

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data						A	X	0.157	336H-70F-

05154 PEN FELT TIP F30J BLACK GID: APXXXX
MANF: BEROL CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data						A	X	00000.02	24H-150F-

69958 PEN FELT TIP PURPLE GID: APXXXX
MANF: SKILCRAFT

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							X	0.452	168H-70F-

80179 PEN FISHER SPACE REFILL P/N PR6 PURPLE MEDIUM POINT GID: FCXXXX
MANF: FISHER PEN

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	3.968	

80180 PEN FISHER SPACE REFILL P/N PR9 LIGHT BLUE MEDIUM POINT GID: FCXXXX
MANF: FISHER PEN

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	4.107	

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005905 3 ■

63766 PEN LUMOCOLOR 313 SF GID: EXXXXX
MANF: STAEDTLER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.2E-6		.36		168H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00000.01	24H-120F-

20744 PEN PARKER 6-234-8 BLACK GID: FCXXXX
MANF: PARKER PEN
....NO TEST DATA AVAILABLE....

60599 PEN PENTEL S520 BLACK GID: FCXXXX
MANF: PENTEL CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.396		00.02	05.30	T SMALL
C	1	025.9	014.3	0.396		00.06	05.30	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.2E-7	19.96	.01		168H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00011.20	

60597 PEN PENTEL S520 BLUE GID: FCXXXX
MANF: PENTEL CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.396		00.02	05.30	T SMALL
C	1	025.9	014.3	0.396		00.06	05.30	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.2E-7	50.19	.03		168H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00010.81	

60598 PEN PENTEL S520 GREEN GID: FCXXXX
MANF: PENTEL CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.396		00.02	05.30	T SMALL
C	1	025.9	014.3	0.396		00.06	05.30	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.2E-7	5.48	.02		168H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00010.21	

20506 PEN PENTEL S520 RED GID: FCXXXX
MANF: PENTEL CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.396		00.03	05.30	T SMALL
C	1	025.9	014.3	0.396		00.06	05.30	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.2E-7	5.52	.00		168H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00011.04	

61068 PEN PM BLACK/E-10 PAPER GID: FCXXXX
MANF: BIC INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00000.79	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005906 5

61589 PEN SHARPIE 3000 BLK GID: FCXXXX
MANF: SANFORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	X	00000.89	

61357 PEN SHARPIE 35001 GID: FCXXXX
MANF: SANFORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
X	X	00017.48	

20610 PEN SPACE B1-PR4F REFILL BLACK GID: FCXXXX
MANF: FISHER PEN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	V	4.284	

63498 PEN UNIMARK 960 GID: APXXXX
MANF: UNI-MARK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	X	7.75	168H-70F-

64856 PENCIL GREASE ON LP4 FILM GID: AKXXXX
MANF: GSA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.004		00.15	08.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	V	00068.25	

64857 PENCIL GREASE WITH VELCRO GID: FCXXXX
MANF: GSA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3			00.03	04.80	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	V	00068.25	

62279 PENCIL SKILCRAFT MECHANICAL GID: FCXXXX
MANF: SKILCRAFT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.315		00.31	03.70	T MOD
X	1	025.9	014.3	0.315		00.12	03.70	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	V	00022.47	

20603 PENCIL STYPTIC
....NO TEST DATA AVAILABLE....

62913 PENETRANT FLUORESCENT P6F-4
MANF: OXY METAL INDUSTRIES

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005907 7

62913 PENETRANT FLUORESCENT P6F-4 (cont)

FLAMMABILITY								FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	14.7	72	-297		02	04

62898 PENETRANT FLUORESCENT P6F-4L
MANF: OXY METAL INDUSTRIES

FLAMMABILITY								FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	14.7	72	-297		0	20

62899 PENETRANT FLUORESCENT P6F-4LNC
MANF: OXY METAL INDUSTRIES

FLAMMABILITY								FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	14.7	72	-297		0	20

62881 PENETRANT I-319
MANF: SHERWIN INC SPEC: MMS-Y-846

FLAMMABILITY								FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	14.7	72	-297		0	20

20239 PENETRANT P-545/DEVELOP D-495A GID: AKXXXX
MANF: URESCO INC

FLAMMABILITY								FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									X	MMH	No test data							
									X	N204								

20240 PENETRANT P-615/DEVELOP D-495A GID: AKXXXX
MANF: URESCO INC

FLAMMABILITY								FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									X	MMH	No test data							
									X	N204								

05460 PIEZD XTLS G1500,G1900 (INORG)
MANF: GULTON INDUSTRIES
....NO TEST DATA AVAILABLE....

62460 PIGMENT GREEN GLOVE BLADDER GID: APXXXX
MANF: PIGMENT DISPERSIONS

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
I	1.2E-6	2.29	.34	.41	24H-70F- 24H-150F-	No test data		

83717 PLASSTIC UBE NYLON 5013B
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

84941 PLASTIC 1-5021
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005908 9

69778 PLASTIC 10% CARBON-GRAPHITE/90% TFE
MANF: CRANE PACKING CO
....NO TEST DATA AVAILABLE....

69673 PLASTIC 1013(1)
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69674 PLASTIC 1014(1,2)
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69675 PLASTIC 1015
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69676 PLASTIC 1016(1,3)
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69677 PLASTIC 1017
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69678 PLASTIC 1103(1)
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69679 PLASTIC 1105(1)
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69772 PLASTIC 12.5% GLASS FIBER/12.5% MOS2/75% TFE
MANF: CRANE PACKING CO
....NO TEST DATA AVAILABLE....

65693 PLASTIC 13N/680
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

65941 PLASTIC 13N/HHS
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

82524 PLASTIC 14B
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

68572 PLASTIC 15% CARBON, PTFE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

69771 PLASTIC 15% GLASS FIBER/5%MOS2/80% TFE
MANF: CRANE PACKING CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005909 0 ■

69714 PLASTIC 1510HC
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69713 PLASTIC 1510LC
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

82108 PLASTIC 1D30HIF
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82109 PLASTIC 1D40
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82110 PLASTIC 1D50
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

68574 PLASTIC 20% GLASS, 5% MOS2, PTFE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

69710 PLASTIC 2000GJ
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69711 PLASTIC 2004MR
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69712 PLASTIC 2085CW
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

82535 PLASTIC 21B 100% REGRIND
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

84242 PLASTIC 224
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

67829 PLASTIC 2401/2180
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67836 PLASTIC 2403 A/B
MANF: APPLIED PLASTICS

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	10.06	.08	2.39	24H-46F- 168H-46F-	No test data		

67835 PLASTIC 2405/2140
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005910 7

Information Handling Services, 2000

67796 PLASTIC 24082
MANF: AMOCO
....NO TEST DATA AVAILABLE....

67818 PLASTIC 2410/2183
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67812 PLASTIC 2411/2311
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67830 PLASTIC 2414/2180
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67831 PLASTIC 2414/2320
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67815 PLASTIC 2415/2180
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67833 PLASTIC 2417/2180
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67825 PLASTIC 2418/2140
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67826 PLASTIC 2421/2140
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67827 PLASTIC 2422/2140
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67828 PLASTIC 2424/2174
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67814 PLASTIC 2425/2305
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67813 PLASTIC 2425/2310
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67816 PLASTIC 2425/2324
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005911 9

67832 PLASTIC 2428/2330
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67821 PLASTIC 2434/2310
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67822 PLASTIC 2434/2320
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67824 PLASTIC 2434/2323
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67823 PLASTIC 2434/2330
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67810 PLASTIC 2438/2180
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67811 PLASTIC 2441/2180
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67819 PLASTIC 2481/2161
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67817 PLASTIC 2482/2192
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67820 PLASTIC 2484/2192
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67837 PLASTIC 2493/2164
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

69779 PLASTIC 25% CARBON-GRAPHITE/75% TFE
MANF: CRANE PACKING CO
....NO TEST DATA AVAILABLE....

67797 PLASTIC 260B1
MANF: AMOCO
....NO TEST DATA AVAILABLE....

67798 PLASTIC 290B1
MANF: AMOCO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F
9999942 0005912 0

Information Handling Services, 2000

DATE: 12/23/88
NON-METALS BY DESIGNATION

82111 PLASTIC 2S30
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

69715 PLASTIC 3002GJ
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69680 PLASTIC 3010
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69716 PLASTIC 3011SO
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69681 PLASTIC 3012
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69682 PLASTIC 3050
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

84243 PLASTIC 306
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

69683 PLASTIC 3060
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

84948 PLASTIC 307
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

69684 PLASTIC 3070
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

84951 PLASTIC 308
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

69685 PLASTIC 3080
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

67800 PLASTIC 3150B
MANF: AMOCO
....NO TEST DATA AVAILABLE....

67801 PLASTIC 3250B
MANF: AMOCO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005913 2

Information Handling Services, 2000

69717 PLASTIC 3303SK
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69686 PLASTIC 3304(4)
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69718 PLASTIC 331050
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69687 PLASTIC 3312
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

67802 PLASTIC 3420B
MANF: AMOCO
....NO TEST DATA AVAILABLE....

69719 PLASTIC 3420CK
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69780 PLASTIC 35% CARBON-GRAPHITE/65% TFE
MANF: CRANE PACKING CO
....NO TEST DATA AVAILABLE....

69720 PLASTIC 3510HC
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

67803 PLASTIC 3550B
MANF: AMOCO
....NO TEST DATA AVAILABLE....

67799 PLASTIC 360B1
MANF: AMOCO
....NO TEST DATA AVAILABLE....

82112 PLASTIC 3D36
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

69776 PLASTIC 40% BRONZE/5% MOS2/55% TFE
MANF: CRANE PACKING CO
....NO TEST DATA AVAILABLE....

69773 PLASTIC 40% BRONZE/60% TFE
MANF: CRANE PACKING CO
....NO TEST DATA AVAILABLE....

67804 PLASTIC 403L3
MANF: AMOCO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005914 4

Information Handling Services, 2000

67805 PLASTIC 404F3
MANF: AMOCO
....NO TEST DATA AVAILABLE....

67806 PLASTIC 408F3
MANF: AMOCO
....NO TEST DATA AVAILABLE....

67807 PLASTIC 4140B
MANF: AMOCO
....NO TEST DATA AVAILABLE....

69380 PLASTIC 46-8012
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

84959 PLASTIC 480
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

69770 PLASTIC 5% GLASS FIBER/5%MOS2/75% TFE
MANF: CRANE PACKING CO
....NO TEST DATA AVAILABLE....

69766 PLASTIC 5% GLASS FIBER/95% TFE
MANF: CRANE PACKING CO
....NO TEST DATA AVAILABLE....

69654 PLASTIC 5003
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69644 PLASTIC 5204
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69645 PLASTIC 5205
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69646 PLASTIC 5207
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69647 PLASTIC 5210
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69648 PLASTIC 5218
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69649 PLASTIC 5225
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005915 6

Information Handling Services, 2000

69650 PLASTIC 5240
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69651 PLASTIC 5260
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

68092 PLASTIC 5311-19
MANF: COLORITE PLASTICS CO.
....NO TEST DATA AVAILABLE....

67834 PLASTIC 5323 A/B
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

69669 PLASTIC 5405
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69670 PLASTIC 5406G
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69671 PLASTIC 5408G
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69672 PLASTIC 5411G
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69655 PLASTIC 5602
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69656 PLASTIC 5603
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69657 PLASTIC 5604
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69661 PLASTIC 5701
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69662 PLASTIC 5703
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69663 PLASTIC 5704 (2)
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005916 8 ■

Information Handling Services, 2000

69664 PLASTIC 5705 (2)
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69665 PLASTIC 5707
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69666 PLASTIC 5713
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69774 PLASTIC 60% BRONZE/40% TFE
MANF: CRANE PACKING CO
....NO TEST DATA AVAILABLE....

69667 PLASTIC 6001C2
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69668 PLASTIC 6003
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69658 PLASTIC 6004
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69659 PLASTIC 6007
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69660 PLASTIC 6009
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

67333 PLASTIC 606/21
MANF: 3M CO
ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67336 PLASTIC 607AA/22NF
MANF: 3M CO
ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67337 PLASTIC 608-10/12N
MANF: 3M CO
ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67338 PLASTIC 608-10TLS/12NLS
MANF: 3M CO
ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005917 T

66656 PLASTIC 610/680
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

66718 PLASTIC 610V/901
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67035 PLASTIC 612B/22NF
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67334 PLASTIC 6164-2/21
MANF: 3M CO
ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67243 PLASTIC 616N/681
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67240 PLASTIC 616N/901
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67244 PLASTIC 618/900C
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

69652 PLASTIC 6206
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

67248 PLASTIC 622/680
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67278 PLASTIC 622/GE
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

69653 PLASTIC 6230
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

84965 PLASTIC 631
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

67279 PLASTIC 638/45
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67342 PLASTIC 6410R/N
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005918 1 ■

Information Handling Services, 2000

67281 PLASTIC 655/555
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

69950 PLASTIC 658/558
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67340 PLASTIC 670/70
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67323 PLASTIC 676F/86
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67324 PLASTIC 677F/70
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67335 PLASTIC 7/308R/M
MANF: 3M CO
ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

69775 PLASTIC 70% BRONZE/30% TFE
MANF: CRANE PACKING CO
....NO TEST DATA AVAILABLE....

69706 PLASTIC 7001DJ
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69707 PLASTIC 7200AF
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69708 PLASTIC 7300GF
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69709 PLASTIC 7300KF
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69688 PLASTIC 8000GK
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69689 PLASTIC 8001KL
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69690 PLASTIC 8004MR
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005919 3

69691 PLASTIC 8004ZR
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

80726 PLASTIC 8007
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

80727 PLASTIC 8016
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

80728 PLASTIC 8020
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

69692 PLASTIC 8020GU
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

80729 PLASTIC 8022
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

80730 PLASTIC 8031
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

80731 PLASTIC 8038
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

80732 PLASTIC 8041
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

80733 PLASTIC 8049
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

80734 PLASTIC 8050
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

80735 PLASTIC 8057
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

80736 PLASTIC 8061
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

80737 PLASTIC 8068
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005920 T

Information Handling Services, 2000

80738 PLASTIC 8072
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

80739 PLASTIC 8079
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

69693 PLASTIC 8080GW
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

80740 PLASTIC 8085
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

80741 PLASTIC 8086
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

69694 PLASTIC 8310GO
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69695 PLASTIC 8310KO
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69696 PLASTIC 8402TO
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69697 PLASTIC 8420HK
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69700 PLASTIC 8462HR
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69701 PLASTIC 8470HU
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69698 PLASTIC 8502HK
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69699 PLASTIC 8602HJ
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

80742 PLASTIC 8659
MANF: APPLIED COMPOSITES
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005921 1

69702 PLASTIC 8752HF
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69703 PLASTIC 8755HK
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69704 PLASTIC 8762HR
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

69705 PLASTIC 8770HU
MANF: NORCHEM
....NO TEST DATA AVAILABLE....

82429 PLASTIC ABSAFIL G1200/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82430 PLASTIC ABSAFIL J1200/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82431 PLASTIC ABSAFIL J1200/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83947 PLASTIC ABSG1FG2
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

65501 PLASTIC ACETAL GID: DKAJXX
MANF: AL-FLA PLACTICS

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	024.5	014.5				04.00	MOD	No test data		No test data							
X	1	024.5	014.5				05.00	MOD										
X	1	030.0	009.0				04.50	MOD										
X	1	030.0	009.0				05.00	MOD										

68548 PLASTIC ACETAL 10% GLASS
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68549 PLASTIC ACETAL 20% GLASS
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68555 PLASTIC ACETAL 21% TFE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

69725 PLASTIC ACETAL COPOLYMER
MANF: NYTEF PLASTICS, LTD.
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005922 3

Information Handling Services, 2000

69726 PLASTIC ACETAL GLASS FILLED
MANF: NYTEF PLASTICS, LTD.
....NO TEST DATA AVAILABLE....

69724 PLASTIC ACETAL HOMOPOLYMER
MANF: NYTEF PLASTICS, LTD.
....NO TEST DATA AVAILABLE....

69364 PLASTIC ACPOL 42-2640
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69363 PLASTIC ACPOL 42-2673
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69365 PLASTIC ACPOL 42-2675
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

82440 PLASTIC ACRYAFIL G40/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82435 PLASTIC ACRYAFIL G40/20/V0
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82437 PLASTIC ACRYAFIL G40/30/V0
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82438 PLASTIC ACRYAFIL G40/35
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

80488 PLASTIC ADELL AB14
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80489 PLASTIC ADELL AB16
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80490 PLASTIC ADELL AB18
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80491 PLASTIC ADELL AF10-660
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80492 PLASTIC ADELL AF10-667
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005923 5

Information Handling Services, 2000

80493 PLASTIC ADELL AF10-667A
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80494 PLASTIC ADELL AF10-667B
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80495 PLASTIC ADELL AG16-662
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80496 PLASTIC ADELL AH18
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80497 PLASTIC ADELL AL18
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80498 PLASTIC ADELL AM10
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80499 PLASTIC ADELL AN38
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80500 PLASTIC ADELL AO16
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80501 PLASTIC ADELL AR13
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80502 PLASTIC ADELL AR14
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80503 PLASTIC ADELL AR16
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80504 PLASTIC ADELL AR18
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80505 PLASTIC ADELL AT13
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80506 PLASTIC ADELL AT14
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005924 7 ■

Information Handling Services, 2000

80507 PLASTIC ADELL AT16
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80508 PLASTIC ADELL BH18
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80509 PLASTIC ADELL BL18
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80510 PLASTIC ADELL BR13
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80511 PLASTIC ADELL BR14
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80512 PLASTIC ADELL BR16
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80513 PLASTIC ADELL BR18
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80514 PLASTIC ADELL BR310
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80515 PLASTIC ADELL BY10
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80516 PLASTIC ADELL EF10
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80517 PLASTIC ADELL EP14
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80518 PLASTIC ADELL EP16
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80519 PLASTIC ADELL ER14
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80520 PLASTIC ADELL ER16
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

80521 PLASTIC ADELL HR36
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80522 PLASTIC ADELL KR14
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80523 PLASTIC ADELL KR16
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

80524 PLASTIC ADELL KR18
MANF: ADELL PLASTICS
....NO TEST DATA AVAILABLE....

67718 PLASTIC AJ50-003
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

80551 PLASTIC AKEMI AP1050
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

80552 PLASTIC AKEMI AP1075
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

80553 PLASTIC AKEMI AP1200
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

80554 PLASTIC AKEMI AP1600
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

85362 PLASTIC AKEMI AP2301
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

80555 PLASTIC AKEMI AP2307
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

80557 PLASTIC AKEMI AP2309
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

80558 PLASTIC AKEMI AP2311
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

80559 PLASTIC AKEMI AP2316 55/45
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F
9999942 0005926 0
Information Handling Services, 2000

80560 PLASTIC AKEMI FILLER 4
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

80561 PLASTIC AKEMI FILLER 7
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

80562 PLASTIC AKULON K222D
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80563 PLASTIC AKULON K222F
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80564 PLASTIC AKULON K223B2P1
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80565 PLASTIC AKULON K223HMS6
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80567 PLASTIC AKULON K224G3
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80568 PLASTIC AKULON K224G5
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80569 PLASTIC AKULON K224G6
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80570 PLASTIC AKULON K224G7
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80566 PLASTIC AKULON K224GO
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80571 PLASTIC AKULON K224HM6
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80572 PLASTIC AKULON M223D
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80573 PLASTIC AKULON M231D1
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

80574 PLASTIC AKULON M238D1
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80575 PLASTIC AKULON M921D
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80576 PLASTIC AKULON S223D
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80577 PLASTIC AKULON S223E
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80578 PLASTIC AKULON S223F
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80580 PLASTIC AKULON S223G3
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80581 PLASTIC AKULON S223G5
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80582 PLASTIC AKULON S223G6
MANF: AKEMI PLASTICS
AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80583 PLASTIC AKULON S223G7
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

80579 PLASTIC AKULON S223GO
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80584 PLASTIC AKULON S223H2G6
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

80585 PLASTIC AKULON S223HM6
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80586 PLASTIC AKULON S223HM8
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80587 PLASTIC AKULON S223HMV7
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005928 4

Information Handling Services, 2000

80588 PLASTIC AKULON S240C
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

85058 PLASTIC ALATHON 20
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85059 PLASTIC ALATHON 20-6064
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85060 PLASTIC ALATHON 2005
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85061 PLASTIC ALATHON 2010
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85062 PLASTIC ALATHON 2020
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85063 PLASTIC ALATHON 2020T
MANF: DUPONT
....NO TEST DATA AVAILABLE....

80828 PLASTIC ALGOFLON 27
MANF: AUSIMONT
....NO TEST DATA AVAILABLE....

80829 PLASTIC ALGOFLON D60V
MANF: AUSIMONT
....NO TEST DATA AVAILABLE....

80830 PLASTIC ALGOFLON DF1
MANF: AUSIMONT
....NO TEST DATA AVAILABLE....

80831 PLASTIC ALGOFLON E2
MANF: AUSIMONT
....NO TEST DATA AVAILABLE....

80832 PLASTIC ALGOFLON F2
MANF: AUSIMONT
....NO TEST DATA AVAILABLE....

69745 PLASTIC ALUMINUM LIQUID
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

69744 PLASTIC ALUMINUM PUTTY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005929 6

Information Handling Services, 2000

69746 PLASTIC ALUMINUM VERY LIQUID
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

67602 PLASTIC AM400 (PCTFE)
MANF: AFTON PLASTICS
....NO TEST DATA AVAILABLE....

80693 PLASTIC AMOCO CRYSTAL POLYSTYRENE G1
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80694 PLASTIC AMOCO CRYSTAL POLYSTYRENE G18
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80695 PLASTIC AMOCO CRYSTAL POLYSTYRENE G2
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80696 PLASTIC AMOCO CRYSTAL POLYSTYRENE G3
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80697 PLASTIC AMOCO CRYSTAL POLYSTYRENE R1
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80698 PLASTIC AMOCO CRYSTAL POLYSTYRENE R2
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80699 PLASTIC AMOCO CRYSTAL POLYSTYRENE R3
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80700 PLASTIC AMOCO CRYSTAL POLYSTYRENE R5
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80701 PLASTIC AMOCO CRYSTAL POLYSTYRENE R7
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80702 PLASTIC AMOCO IMPACT POLYSTYRENE H2R
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80703 PLASTIC AMOCO IMPACT POLYSTYRENE H3E
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80704 PLASTIC AMOCO IMPACT POLYSTYRENE H4E
MANF: AMOCO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005930 2 ■

Information Handling Services, 2000

80705 PLASTIC AMOCO IMPACT POLYSTYRENE H4R
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80706 PLASTIC AMOCO IMPACT POLYSTYRENE HXM
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80707 PLASTIC AMOCO IMPACT POLYSTYRENE M9
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80708 PLASTIC AMOCO IMPACT POLYSTYRENE M9R
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80709 PLASTIC AMOCO POLYPROPYLENE 4017
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80710 PLASTIC AMOCO POLYPROPYLENE 4018
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80711 PLASTIC AMOCO POLYPROPYLENE 4036
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80712 PLASTIC AMOCO POLYPROPYLENE 4039
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80713 PLASTIC AMOCO POLYPROPYLENE 4046
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80714 PLASTIC AMOCO POLYPROPYLENE 4222
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80715 PLASTIC AMOCO POLYPROPYLENE 4228
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80716 PLASTIC AMOCO POLYPROPYLENE 5219
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80717 PLASTIC AMOCO POLYPROPYLENE 7232
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80718 PLASTIC AMOCO POLYPROPYLENE 7234
MANF: AMOCO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005931 4

Information Handling Services, 2000

80723 PLASTIC AMOCO POLYPROPYLENE CR22 NA
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80725 PLASTIC AMOCO POLYPROPYLENE CR35 A
MANF: AMOCO
....NO TEST DATA AVAILABLE....

80724 PLASTIC AMOCO POLYPROPYLENE CR35 NA
MANF: AMOCO
....NO TEST DATA AVAILABLE....

68425 PLASTIC AN20GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68426 PLASTIC AN30GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68427 PLASTIC AN40GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

67687 PLASTIC AP1001-4 FILLER PASTE #4
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67688 PLASTIC AP1001-7 AKEMI FILLER NO 7
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67604 PLASTIC AP1500 SPRAYABLE PRIMAFILL
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67700 PLASTIC AP2206 SURFACE COAT
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67701 PLASTIC AP2209 EPOXY SURFACE COAT
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67702 PLASTIC AP2211 EPOXY SURFACE COAT AND CASTING RESIN
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67703 PLASTIC AP2220 HIGH-TEMP SURFACE EPOXY
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67704 PLASTIC AP2308 EPOXY MASS CASTING
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005932 6

Information Handling Services, 2000

67705 PLASTIC AP2312 SURFACE CASTING
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67706 PLASTIC AP2316 SURFACE CASTING
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67707 PLASTIC AP2320 HI-TEMP EPOXY CASTING
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67699 PLASTIC AP3030 COLD SOLDER TYPE FILLER PASTE
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67711 PLASTIC AP3031 GLAZING COMPOUND
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67841 PLASTIC APCO 1475
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67839 PLASTIC APCO 5290
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67840 PLASTIC APCO 5293
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67842 PLASTIC APCO 5303
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67843 PLASTIC APCO 5313
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67846 PLASTIC APCO 5314
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67808 PLASTIC APCO 5321
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67809 PLASTIC APCO 5323
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67845 PLASTIC APCO 5363
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005933 8

Information Handling Services, 2000

67838 PLASTIC APCO 5393
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

67844 PLASTIC APCO 5823
MANF: APPLIED PLASTICS
....NO TEST DATA AVAILABLE....

83160 PLASTIC APEX 1001
MANF: APEX
....NO TEST DATA AVAILABLE....

83161 PLASTIC APEX 1002
MANF: APEX
....NO TEST DATA AVAILABLE....

83162 PLASTIC APEX 1003
MANF: APEX
....NO TEST DATA AVAILABLE....

83163 PLASTIC APEX 1004
MANF: APEX
....NO TEST DATA AVAILABLE....

83164 PLASTIC APEX 1007
MANF: APEX
....NO TEST DATA AVAILABLE....

83165 PLASTIC APEX 1008
MANF: APEX
....NO TEST DATA AVAILABLE....

83166 PLASTIC APEX 1009
MANF: APEX
....NO TEST DATA AVAILABLE....

83167 PLASTIC APEX 1011
MANF: APEX
....NO TEST DATA AVAILABLE....

83168 PLASTIC APEX 1013
MANF: APEX
....NO TEST DATA AVAILABLE....

83169 PLASTIC APEX 1015
MANF: APEX
....NO TEST DATA AVAILABLE....

83170 PLASTIC APEX 1216
MANF: APEX
....NO TEST DATA AVAILABLE....

83171 PLASTIC APEX 1217
MANF: APEX
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005934 T ■

Information Handling Services, 2000

83172 PLASTIC APEX 1221
MANF: APEX
....NO TEST DATA AVAILABLE....

83173 PLASTIC APEX 1369
MANF: APEX
....NO TEST DATA AVAILABLE....

83174 PLASTIC APEX 1464
MANF: APEX
....NO TEST DATA AVAILABLE....

83175 PLASTIC APEX 1521
MANF: APEX
....NO TEST DATA AVAILABLE....

83176 PLASTIC APEX 1522
MANF: APEX
....NO TEST DATA AVAILABLE....

83177 PLASTIC APEX 1523
MANF: APEX
....NO TEST DATA AVAILABLE....

83178 PLASTIC APEX 1524
MANF: APEX
....NO TEST DATA AVAILABLE....

83179 PLASTIC APEX 1525
MANF: APEX
....NO TEST DATA AVAILABLE....

83180 PLASTIC APEX 1526
MANF: APEX
....NO TEST DATA AVAILABLE....

83181 PLASTIC APEX 1527
MANF: APEX
....NO TEST DATA AVAILABLE....

83182 PLASTIC APEX 1560
MANF: APEX
....NO TEST DATA AVAILABLE....

83183 PLASTIC APEX 1561
MANF: APEX
....NO TEST DATA AVAILABLE....

83184 PLASTIC APEX 1562
MANF: APEX
....NO TEST DATA AVAILABLE....

83185 PLASTIC APEX 1563
MANF: APEX
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005935 1

83186 PLASTIC APEX 1564
MANF: APEX
....NO TEST DATA AVAILABLE....

83187 PLASTIC APEX 1565
MANF: APEX
....NO TEST DATA AVAILABLE....

83188 PLASTIC APEX 1566
MANF: APEX
....NO TEST DATA AVAILABLE....

83189 PLASTIC APEX 1581
MANF: APEX
....NO TEST DATA AVAILABLE....

83190 PLASTIC APEX 1582
MANF: APEX
....NO TEST DATA AVAILABLE....

83191 PLASTIC APEX 1583
MANF: APEX
....NO TEST DATA AVAILABLE....

83192 PLASTIC APEX 1584
MANF: APEX
....NO TEST DATA AVAILABLE....

83193 PLASTIC APEX 1585
MANF: APEX
....NO TEST DATA AVAILABLE....

83194 PLASTIC APEX 1586
MANF: APEX
....NO TEST DATA AVAILABLE....

83195 PLASTIC APEX 1587
MANF: APEX
....NO TEST DATA AVAILABLE....

83196 PLASTIC APEX 1589
MANF: APEX
....NO TEST DATA AVAILABLE....

83197 PLASTIC APEX 1590
MANF: APEX
....NO TEST DATA AVAILABLE....

83198 PLASTIC APEX 1835
MANF: APEX
....NO TEST DATA AVAILABLE....

83199 PLASTIC APEX 1850
MANF: APEX
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005936 3 ■

Information Handling Services, 2000

83200 PLASTIC APEX 1877
MANF: APEX
....NO TEST DATA AVAILABLE....

83201 PLASTIC APEX 370
MANF: APEX
....NO TEST DATA AVAILABLE....

83202 PLASTIC APEX 4101
MANF: APEX
....NO TEST DATA AVAILABLE....

83203 PLASTIC APEX 4103
MANF: APEX
....NO TEST DATA AVAILABLE....

83204 PLASTIC APEX 4109
MANF: APEX
....NO TEST DATA AVAILABLE....

83205 PLASTIC APEX 4217
MANF: APEX
....NO TEST DATA AVAILABLE....

83206 PLASTIC APEX 776
MANF: APEX
....NO TEST DATA AVAILABLE....

67847 PLASTIC ARLOY 1000
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67848 PLASTIC ARLOY 1100
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67849 PLASTIC ARLOY 1200
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67850 PLASTIC ARLOY 2000
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

80589 PLASTIC ARNITEL 40D G1 G6
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80590 PLASTIC ARNITEL 46D G1 G6
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80591 PLASTIC ARNITEL 55D G1 G6
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005937 5

80593 PLASTIC ARNITEL 74D G1 G6
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80594 PLASTIC ARNITEL EL550
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80595 PLASTIC ARNITEL EL630
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80596 PLASTIC ARNITEL EL740
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80597 PLASTIC ARNITEL EM400
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

80598 PLASTIC ARNITEL EM460
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

68405 PLASTIC AS15CF1000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

67874 PLASTIC ASHLENE 520
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67875 PLASTIC ASHLENE 521
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67876 PLASTIC ASHLENE 522
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67870 PLASTIC ASHLENE 525LD
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67880 PLASTIC ASHLENE 525LD 13G
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67871 PLASTIC ASHLENE 527LD
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67873 PLASTIC ASHLENE 528BR
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005938 7 ■

Information Handling Services, 2000

67877 PLASTIC ASHLENE 528L 13G
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67878 PLASTIC ASHLENE 528L 25G
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67879 PLASTIC ASHLENE 528L 33G
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67869 PLASTIC ASHLENE 528LW
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67872 PLASTIC ASHLENE 528MS
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67889 PLASTIC ASHLENE 538
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67890 PLASTIC ASHLENE 541
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67888 PLASTIC ASHLENE 630
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67886 PLASTIC ASHLENE 734D
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67885 PLASTIC ASHLENE 735D
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67893 PLASTIC ASHLENE 737
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67887 PLASTIC ASHLENE 738D
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67892 PLASTIC ASHLENE 741
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67883 PLASTIC ASHLENE 830L
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005939 9

Information Handling Services, 2000

67881 PLASTIC ASHLENE 830L 13G
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67882 PLASTIC ASHLENE 830L 33G
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67884 PLASTIC ASHLENE 830LN
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

67891 PLASTIC ASHLENE 840
MANF: ASHLEY POLYMERS INC
....NO TEST DATA AVAILABLE....

80526 PLASTIC ASTRAGLAS K
MANF: AEROMAT PLASTICS
....NO TEST DATA AVAILABLE....

80527 PLASTIC ASTRAGLAS N
MANF: AEROMAT PLASTICS
....NO TEST DATA AVAILABLE....

80528 PLASTIC ASTRAGLAS NG
MANF: AEROMAT PLASTICS
....NO TEST DATA AVAILABLE....

68406 PLASTIC AT20GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68407 PLASTIC AT30GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68408 PLASTIC AT40GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

80767 PLASTIC ATLAS POLYETHYLENE (LINEAR)
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

80768 PLASTIC ATLAS POLYPROPYLENE HOMOPOLYMER
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

80769 PLASTIC ATLAS POLYPROPYLENE V0 HOMOPOLYMER
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

80770 PLASTIC ATLAS POLYPROPYLENE V2 HOMOPOLYMER
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005940 5

Information Handling Services, 2000

80771 PLASTIC ATLAS PVC T2
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

80772 PLASTIC ATLASTAFLEX PVC SHEET MEMBRANE
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

83720 PLASTIC BAKELITE DPD6169 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83721 PLASTIC BAKELITE DPDA6479 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83722 PLASTIC BAKELITE DQDA6479 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83723 PLASTIC BAKELITE DQDA6480 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83724 PLASTIC BAKELITE OPDA9169 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

81560 PLASTIC BAYBLEND
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81562 PLASTIC BAYBLEND DP2-1439
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81563 PLASTIC BAYBLEND DP2-1440
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81564 PLASTIC BAYBLEND DP2-1441
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81566 PLASTIC BAYBLEND DP2-1482
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81568 PLASTIC BAYBLEND DP2-1483
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81569 PLASTIC BAYBLEND DP2-1484
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005941 7

81571 PLASTIC BAYBLEND MC2500
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81573 PLASTIC BAYBLEND MC3200
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81574 PLASTIC BAYBLEND MH6570
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81576 PLASTIC BAYBLEND MH6580
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81578 PLASTIC BAYBLEND MH6595
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81579 PLASTIC BAYBLEND MJ2500
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81580 PLASTIC BAYBLEND UT1018
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

67974 PLASTIC BLANE 2150
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67975 PLASTIC BLANE 2153
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67976 PLASTIC BLANE 2202
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67977 PLASTIC BLANE 2234
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67978 PLASTIC BLANE 2249
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67969 PLASTIC BLANE 309
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67970 PLASTIC BLANE 375
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005942 9

Information Handling Services, 2000

67979 PLASTIC BLANK 7191
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67980 PLASTIC BLANK 8100
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67971 PLASTIC BLANK 8105
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67972 PLASTIC BLANK 830
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67973 PLASTIC BLANK 851
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67981 PLASTIC BLANK 9148
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67982 PLASTIC BLANK 9202-1
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67950 PLASTIC BLENDING PVC RESINS VC260C
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67951 PLASTIC BLENDING PVC RESINS VC260S
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67952 PLASTIC BLENDING PVC RESINS VC260SS
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67949 PLASTIC BLENDING PVC RESINS VC265
MANF: BORDEN
....NO TEST DATA AVAILABLE....

81004 PLASTIC BMC100
MANF: BMC INC
....NO TEST DATA AVAILABLE....

81005 PLASTIC BMC1000
MANF: BMC INC
....NO TEST DATA AVAILABLE....

81006 PLASTIC BMC102
MANF: BMC INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005943 0

Information Handling Services, 2000

81007 PLASTIC BMC200
MANF: BMC INC
....NO TEST DATA AVAILABLE....

81008 PLASTIC BMC300
MANF: BMC INC
....NO TEST DATA AVAILABLE....

81009 PLASTIC BMC400
MANF: BMC INC
....NO TEST DATA AVAILABLE....

81010 PLASTIC BMC404
MANF: BMC INC
....NO TEST DATA AVAILABLE....

81011 PLASTIC BMC500
MANF: BMC INC
....NO TEST DATA AVAILABLE....

81012 PLASTIC BMC700
MANF: BMC INC

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.23	.04	.00	

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
No test data			

81013 PLASTIC BMC800
MANF: BMC INC
....NO TEST DATA AVAILABLE....

81014 PLASTIC BMC900
MANF: BMC INC
....NO TEST DATA AVAILABLE....

81015 PLASTIC BMC902
MANF: BMC INC
....NO TEST DATA AVAILABLE....

60661 PLASTIC BM101 ACRYLIC PVC GID: DKAKXX
MANF: DUPONT

FLAMMABILITY																	
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.125			01.40	NONE	No test data		No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	3.7E-6	.41	.01		

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
X	A	00020.23	

69747 PLASTIC BRONZE PUTTY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

69777 PLASTIC BRONZE/5% MOS2/40% TFE
MANF: CRANE PACKING CO
....NO TEST DATA AVAILABLE....

69754 PLASTIC BRUSHABLE CERAMIC COMPOUND
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005944 2

84533 PLASTIC C60 STD
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84534 PLASTIC C61 STD
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84535 PLASTIC C9-4183/HD3485
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84536 PLASTIC C9-4186/HD3485
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84414 PLASTIC CADCO ABS NATURAL
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

84415 PLASTIC CADCO ACRYLIC PMM CAST
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

69793 PLASTIC CADCO CAST ACRYLIC
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

84416 PLASTIC CADCO LEXAN POLYCARBONATE EXTRUDED
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

69788 PLASTIC CADCO MD POLYAMIDE MDS2 FILL
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

69787 PLASTIC CADCO NSM POLYAMIDE FILLED 6
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

69782 PLASTIC CADCO NYLON CBL
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

69781 PLASTIC CADCO NYLON CMD
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

69769 PLASTIC CADCO NYLON CNT
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

84417 PLASTIC CADCO POLYPROPYLENE NATURAL
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005945 4

84418 PLASTIC CADCO POLYSTYRENE HI-IMPACT
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

84419 PLASTIC CADCO PVC RIGID
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

84420 PLASTIC CADCO TEFLON PTFE VIRGIN
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

69785 PLASTIC CADCO TYPE 6
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

69784 PLASTIC CADCO TYPE 6/6
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

69792 PLASTIC CADCO UHMW
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

81413 PLASTIC CADON 112
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

81415 PLASTIC CADON 127
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

81416 PLASTIC CADON 135FG
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

81418 PLASTIC CADON 140
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

81419 PLASTIC CADON 160
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

81420 PLASTIC CADON 161
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

81422 PLASTIC CADON 2100
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

81421 PLASTIC CADON FRX
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005946 6

Information Handling Services, 2000

81423 PLASTIC CADON G1606
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

81424 PLASTIC CADON G2110
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

81425 PLASTIC CADON G2120
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84756 PLASTIC CALIBRE 200-10
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84757 PLASTIC CALIBRE 200-15
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84758 PLASTIC CALIBRE 200-22
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84759 PLASTIC CALIBRE 200-4
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84760 PLASTIC CALIBRE 200-6
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84762 PLASTIC CALIBRE 2060-10
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84763 PLASTIC CALIBRE 2060-15
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84764 PLASTIC CALIBRE 2060-22
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84765 PLASTIC CALIBRE 2060-4
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84766 PLASTIC CALIBRE 2060-6
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84767 PLASTIC CALIBRE 2080-15
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005947 8

Information Handling Services, 2000

84768 PLASTIC CALIBRE 2080-4
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84769 PLASTIC CALIBRE 300-10
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84770 PLASTIC CALIBRE 300-15
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84771 PLASTIC CALIBRE 300-22
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84772 PLASTIC CALIBRE 300-4
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84774 PLASTIC CALIBRE 300-6
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84776 PLASTIC CALIBRE 510
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84778 PLASTIC CALIBRE 550
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84780 PLASTIC CALIBRE 700-10
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84782 PLASTIC CALIBRE 700-15
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84783 PLASTIC CALIBRE 700-6
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84784 PLASTIC CALIBRE 800-10
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84787 PLASTIC CALIBRE 800-15
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84789 PLASTIC CALIBRE 800-6
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005948 T

Information Handling Services, 2000

67752 PLASTIC CAPRON 8200
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67753 PLASTIC CAPRON 8202
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67755 PLASTIC CAPRON 8202C
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67756 PLASTIC CAPRON 8202CL
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67754 PLASTIC CAPRON 8202L
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67758 PLASTIC CAPRON 8203G
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67760 PLASTIC CAPRON 8220HS
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67759 PLASTIC CAPRON 8221HS
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67748 PLASTIC CAPRON 8230G HS
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67762 PLASTIC CAPRON 8231G HS
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67749 PLASTIC CAPRON 8233G HS
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67744 PLASTIC CAPRON 8234G HS
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67741 PLASTIC CAPRON 8253
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67742 PLASTIC CAPRON 8254
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005949 1

Information Handling Services, 2000

67743 PLASTIC CAPRON 8255
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67746 PLASTIC CAPRON 8259
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67750 PLASTIC CAPRON 8260
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67745 PLASTIC CAPRON 8266G HS
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

80612 PLASTIC CAPRON 8267G
MANF: ALLIED FIBERS
....NO TEST DATA AVAILABLE....

67751 PLASTIC CAPRON 8270
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67761 PLASTIC CAPRON 8276G HS
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67747 PLASTIC CAPRON 8350
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67757 PLASTIC CAPRON 8360
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

69749 PLASTIC CARBIDE PUTTY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

69565 PLASTIC CAST ACRYLIC
....NO TEST DATA AVAILABLE....

69786 PLASTIC CAST NYLON POLYAMIDE TYPE 6
MANF: CADILLAC PLASTICS

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	3.40	.17	.00		No test data		

85307 PLASTIC CELANEX 2000
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85308 PLASTIC CELANEX 2000K
MANF: CELANESE
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005950 8 ■

Information Handling Services, 2000

85309 PLASTIC CELANEX 2002
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85310 PLASTIC CELANEX 2002K
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85311 PLASTIC CELANEX 2003K
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85312 PLASTIC CELANEX 2012
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85313 PLASTIC CELANEX 3112
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85314 PLASTIC CELANEX 3200
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85315 PLASTIC CELANEX 3210
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85316 PLASTIC CELANEX 3211
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85317 PLASTIC CELANEX 3300
MANF: CELANESE
....NO TEST DATA AVAILABLE....

62233 PLASTIC CELANEX 3310 GID: BCIAFW
MANF: AMP INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00002.37	

TOXICITY

85318 PLASTIC CELANEX 3310
MANF: CELANESE
....NO TEST DATA AVAILABLE....

05380 PLASTIC CELANEX 3310/GL/POLYE GID: FJCBXX
MANF: CELANESE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	
C	2	023.8	014.5	0.125			00.10		NONE
C	1	023.8	014.5	0.125		00.02	04.00	T	NONE
I	1	030.0	010.0	0.121		00.10	08.50	T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.8E-7	.19	.04		

ODOR

RT	RT	WEIGHT	CURE
A	A	00010.11	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005951 T

85319 PLASTIC CELANEX 3311
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85320 PLASTIC CELANEX 3400
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85321 PLASTIC CELANEX 4300
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85322 PLASTIC CELANEX 4330
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85323 PLASTIC CELANEX 5300
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85324 PLASTIC CELANEX 6400
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85325 PLASTIC CELANEX 7700
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85326 PLASTIC CELCON AS270
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85327 PLASTIC CELCON AS450
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85328 PLASTIC CELCON GB25
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85329 PLASTIC CELCON GC25A GLASS COUPLED
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85330 PLASTIC CELCON M25
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85331 PLASTIC CELCON M270
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85332 PLASTIC CELCON M90
MANF: CELANESE
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005952 1 ■

Information Handling Services, 2000

85334 PLASTIC CELCON MC270HM
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85336 PLASTIC CELCON MC90HM
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85337 PLASTIC CELCON WR25
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85338 PLASTIC CELCON WR90
MANF: CELANESE
....NO TEST DATA AVAILABLE....

69752 PLASTIC CERAMIC WEAR COMPOUND
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

84649 PLASTIC CG1310R/RP1520H
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84652 PLASTIC CGL1310R/RP1520H
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84655 PLASTIC CGL1320R/RP1500H
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84690 PLASTIC CGL1320R/RP1520H
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

68003 PLASTIC CHEMCOR EMULSION 2-67A
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

85346 PLASTIC CHEMCOR PARAFFIN EMULSION 135-50
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

85347 PLASTIC CHEMCOR POLY EMULSION 286
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

68009 PLASTIC CHEMCOR ZAC
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

81117 PLASTIC CHEMLOK 210
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005953 3

Information Handling Services, 2000

81093 PLASTIC CHEMLOK 218
MANF: LORD CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	15.72	.49	.00	24H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

81886 PLASTIC CHEMTROL PP TYPE 1
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

05121 PLASTIC CHLORINATED POLYETHER GID: DKBBXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		020.9	014.7					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.4E-6	.06	.00		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.00	

TOXICITY

69493 PLASTIC CLEARSTUF 1006
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

69485 PLASTIC CLEARSTUF 5901
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

69486 PLASTIC CLEARSTUF 7202
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

69487 PLASTIC CLEARSTUF 7204
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

69488 PLASTIC CLEARSTUF 7207
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

81884 PLASTIC CLEARSTUF 8002
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

69489 PLASTIC CLEARSTUF 8006
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

69490 PLASTIC CLEARSTUF 8403
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

69491 PLASTIC CLEARSTUF 9504
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

69492 PLASTIC CLEARSTUF 9506
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005954 5

68371 PLASTIC COMALLOY 110-1120
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68378 PLASTIC COMALLOY 110-1140
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68372 PLASTIC COMALLOY 110-1220
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68379 PLASTIC COMALLOY 110-1240
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68374 PLASTIC COMALLOY 110-1540
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68375 PLASTIC COMALLOY 110-3010
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68376 PLASTIC COMALLOY 110-3020
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68370 PLASTIC COMALLOY 110-3030
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68377 PLASTIC COMALLOY 110-3040
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68388 PLASTIC COMALLOY 120-2430
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68397 PLASTIC COMALLOY 130-3020
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68398 PLASTIC COMALLOY 130-3040
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68384 PLASTIC COMALLOY 140-2140
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68401 PLASTIC COMALLOY 140-2250
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005955 7

68385 PLASTIC COMALLOY 140-2355
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68382 PLASTIC COMALLOY 140-3010
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68399 PLASTIC COMALLOY 140-3020
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68381 PLASTIC COMALLOY 140-3030
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68400 PLASTIC COMALLOY 140-3040
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68402 PLASTIC COMALLOY 170-3020
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68386 PLASTIC COMALLOY 170-3030
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68403 PLASTIC COMALLOY 170-3040
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68387 PLASTIC COMALLOY 210-3020
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68404 PLASTIC COMALLOY 210-3030
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68315 PLASTIC COMALLOY 220-3010
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68342 PLASTIC COMALLOY 220-3020
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68316 PLASTIC COMALLOY 220-3030
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68343 PLASTIC COMALLOY 220-3040
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005956 9 ■

Information Handling Services, 2000

68317 PLASTIC COMALLOY 240-3020
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68344 PLASTIC COMALLOY 240-3030
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68318 PLASTIC COMALLOY 240-3040
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68345 PLASTIC COMALLOY 260-3020
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68319 PLASTIC COMALLOY 260-3030
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68346 PLASTIC COMALLOY 310-3010
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68320 PLASTIC COMALLOY 310-3015
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68347 PLASTIC COMALLOY 310-3020
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68323 PLASTIC COMALLOY 410-2140
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68326 PLASTIC COMALLOY 410-2140-100
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68350 PLASTIC COMALLOY 410-2250
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68353 PLASTIC COMALLOY 410-2250-100
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68324 PLASTIC COMALLOY 410-2355
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68321 PLASTIC COMALLOY 410-3015
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005957 0

Information Handling Services, 2000

68351 PLASTIC COMALLOY 410-3015-100
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68348 PLASTIC COMALLOY 410-3030
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68325 PLASTIC COMALLOY 410-3030-100
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68322 PLASTIC COMALLOY 410-3045
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68352 PLASTIC COMALLOY 410-3045-100
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68349 PLASTIC COMALLOY 410-3055
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68329 PLASTIC COMALLOY 510-1515
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68356 PLASTIC COMALLOY 510-2615
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68327 PLASTIC COMALLOY 510-3010
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68354 PLASTIC COMALLOY 510-3024
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68328 PLASTIC COMALLOY 510-3030
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68355 PLASTIC COMALLOY 510-3040
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68330 PLASTIC COMALLOY 515-1000
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68333 PLASTIC COMALLOY 610-2140
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005958 2

Information Handling Services, 2000

68360 PLASTIC COMALLOY 610-2250
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68334 PLASTIC COMALLOY 610-2355
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68357 PLASTIC COMALLOY 610-3013
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68331 PLASTIC COMALLOY 610-3020
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68358 PLASTIC COMALLOY 610-3033
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68332 PLASTIC COMALLOY 610-3043
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68359 PLASTIC COMALLOY 610-3050
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68363 PLASTIC COMALLOY 620-1540
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68337 PLASTIC COMALLOY 620-2140
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68367 PLASTIC COMALLOY 620-2140-100
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68364 PLASTIC COMALLOY 620-2250
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68338 PLASTIC COMALLOY 620-2355
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68361 PLASTIC COMALLOY 620-3013
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68365 PLASTIC COMALLOY 620-3013-100
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005959 4 ■

Information Handling Services, 2000

68335 PLASTIC COMALLOY 620-3020
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68339 PLASTIC COMALLOY 620-3020-100
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68366 PLASTIC COMALLOY 620-3033-100
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68362 PLASTIC COMALLOY 620-3043
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68340 PLASTIC COMALLOY 620-3043-100
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68336 PLASTIC COMALLOY 620-3050
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68309 PLASTIC COMALLOY 640-2140
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68300 PLASTIC COMALLOY 640-2250
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68310 PLASTIC COMALLOY 640-2355
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68307 PLASTIC COMALLOY 640-3020
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68298 PLASTIC COMALLOY 640-3033
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68308 PLASTIC COMALLOY 640-3043
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68299 PLASTIC COMALLOY 640-3050
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68341 PLASTIC COMALLOY 660-3013
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005960 0

Information Handling Services, 2000

68368 PLASTIC COMALLOY 660-3020
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68296 PLASTIC COMALLOY 660-3033
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68297 PLASTIC COMALLOY 660-3043
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68306 PLASTIC COMALLOY 660-3050
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68313 PLASTIC COMALLOY 710-2140
MANF: CQMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68303 PLASTIC COMALLOY 710-2250
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68312 PLASTIC COMALLOY 710-2355
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68301 PLASTIC COMALLOY 710-3030
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

84177 PLASTIC COMALLOY 710-3040
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68302 PLASTIC COMALLOY 710-3050
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68304 PLASTIC COMALLOY 740-3020
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68314 PLASTIC COMALLOY 740-3030
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

68305 PLASTIC COMALLOY 740-3040
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

84181 PLASTIC COMALLOY HILOY 610
MANF: COMALLOY INTERNATIONAL CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005961 2

68540 PLASTIC COMPOUND 954
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

84298 PLASTIC CONAPOXY TE1257/EA071
MANF: CONAP
....NO TEST DATA AVAILABLE....

84299 PLASTIC CONAPOXY TE1257/EA08
MANF: CONAP
....NO TEST DATA AVAILABLE....

84300 PLASTIC CONAPOXY TE1257/EA113
MANF: CONAP
....NO TEST DATA AVAILABLE....

84301 PLASTIC CONAPOXY TE1257/EA116
MANF: CONAP
....NO TEST DATA AVAILABLE....

84302 PLASTIC CONAPOXY TE1257/EA117
MANF: CONAP
....NO TEST DATA AVAILABLE....

68395 PLASTIC COPO 1507
MANF: COPOLYMER RUBBER AND CHEM CORP
....NO TEST DATA AVAILABLE....

67944 PLASTIC COPOLYMER PVC RESIN VC113
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67943 PLASTIC COPOLYMER PVC RESIN VC113K
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67945 PLASTIC COPOLYMER PVC RESIN VC113R
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67946 PLASTIC COPOLYMER PVC RESIN VC168
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67947 PLASTIC COPOLYMER PVC RESIN VC171
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67948 PLASTIC COPOLYMER PVC RESIN VC172
MANF: BORDEN
....NO TEST DATA AVAILABLE....

68502 PLASTIC COSDEN 500
MANF: COSDEN OIL & CHEMICAL CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005962 4

Information Handling Services, 2000

68503 PLASTIC COSDEN 525
MANF: COSDEN OIL & CHEMICAL CO
....NO TEST DATA AVAILABLE....

68504 PLASTIC COSDEN 535
MANF: COSDEN OIL & CHEMICAL CO
....NO TEST DATA AVAILABLE....

68505 PLASTIC COSDEN 550
MANF: COSDEN OIL & CHEMICAL CO
....NO TEST DATA AVAILABLE....

68506 PLASTIC COSDEN 560
MANF: COSDEN OIL & CHEMICAL CO
....NO TEST DATA AVAILABLE....

68507 PLASTIC COSDEN 625
MANF: COSDEN OIL & CHEMICAL CO
....NO TEST DATA AVAILABLE....

68508 PLASTIC COSDEN 680
MANF: COSDEN OIL & CHEMICAL CO
....NO TEST DATA AVAILABLE....

68509 PLASTIC COSDEN 740
MANF: COSDEN OIL & CHEMICAL CO
....NO TEST DATA AVAILABLE....

68510 PLASTIC COSDEN 825
MANF: COSDEN OIL & CHEMICAL CO
....NO TEST DATA AVAILABLE....

68511 PLASTIC COSDEN 825E
MANF: COSDEN OIL & CHEMICAL CO
....NO TEST DATA AVAILABLE....

68512 PLASTIC COSDEN 945
MANF: COSDEN OIL & CHEMICAL CO
....NO TEST DATA AVAILABLE....

68389 PLASTIC CP41
MANF: CONTINENTAL POLYMERS INC
....NO TEST DATA AVAILABLE....

68390 PLASTIC CP51
MANF: CONTINENTAL POLYMERS INC
....NO TEST DATA AVAILABLE....

68391 PLASTIC CP61
MANF: CONTINENTAL POLYMERS INC
....NO TEST DATA AVAILABLE....

68392 PLASTIC CP80
MANF: CONTINENTAL POLYMERS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005963 6

Information Handling Services, 2000

68393 PLASTIC CP81
MANF: CONTINENTAL POLYMERS INC
....NO TEST DATA AVAILABLE....

68394 PLASTIC CP82
MANF: CONTINENTAL POLYMERS INC
....NO TEST DATA AVAILABLE....

69521 PLASTIC CPVC TYPE 4
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

84921 PLASTIC CR39
MANF: PPG INDUSTRIES
....NO TEST DATA AVAILABLE....

69563 PLASTIC CROSSLINKED POLYSTYRENE Q2005
....NO TEST DATA AVAILABLE....

68014 PLASTIC CTFE
MANF: CHEMPLAST
....NO TEST DATA AVAILABLE....

84349 PLASTIC CTI ABS AS10GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

84350 PLASTIC CTI ABS AS20GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

84351 PLASTIC CTI ABS AS30GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

84352 PLASTIC CTI ABS AS40GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

84260 PLASTIC CTI NYLON 6/6 NN60CF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

84261 PLASTIC CTI NYLON 6/6 NN60GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

84262 PLASTIC CTI PEEK PK20CF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

84263 PLASTIC CTI POLYSULFONE PF30F/15T
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

84264 PLASTIC CTI SAN SN20GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005964 8 ■

Information Handling Services, 2000

84265 PLASTIC CTI SAN SN30GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

84266 PLASTIC CTI SAN SN40GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

81016 PLASTIC CYCOLAC AR
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81017 PLASTIC CYCOLAC DFA-R
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81018 PLASTIC CYCOLAC DH
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81019 PLASTIC CYCOLAC EP3510
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81020 PLASTIC CYCOLAC EPB3570
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81021 PLASTIC CYCOLAC ETS3540
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

05441 PLASTIC CYCOLAC GRT GID: EFAIXX
MANF: BORG WARNER

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	0.098		00.09	08.90	MOD	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	3.6E-6	.75	.00			A	A	00020.18	

81022 PLASTIC CYCOLAC GSM
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81023 PLASTIC CYCOLAC HM
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81024 PLASTIC CYCOLAC KJB
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81025 PLASTIC CYCOLAC KJM
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005965 T

81026 PLASTIC CYCOLAC KJT
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81027 PLASTIC CYCOLAC KJU
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81028 PLASTIC CYCOLAC KJW
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81029 PLASTIC CYCOLAC L
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81030 PLASTIC CYCOLAC LXB
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81031 PLASTIC CYCOLAC T
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81032 PLASTIC CYCOLAC TA
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81033 PLASTIC CYCOLAC X11
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81036 PLASTIC CYCOLAC X15
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81034 PLASTIC CYCOLAC X17
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81035 PLASTIC CYCOLAC X37
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81037 PLASTIC CYCOLAC Z48
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81038 PLASTIC CYCOLAC Z86
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81039 PLASTIC CYCOLAC ZA2
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005966 1

Information Handling Services, 2000

81040 PLASTIC CYCOLAC ZA4
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81041 PLASTIC CYCOLAC ZA7
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81042 PLASTIC CYCOLOY EHA
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81043 PLASTIC CYCOVIN CTB
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81044 PLASTIC CYCOVIN K20
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81045 PLASTIC CYCOVIN K29
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

67787 PLASTIC CYGLAS 508
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

67785 PLASTIC CYGLAS 600
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

67786 PLASTIC CYGLAS 605
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

67784 PLASTIC CYGLAS 610
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

67781 PLASTIC CYGLAS 615
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

67783 PLASTIC CYGLAS 620
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

67782 PLASTIC CYGLAS 620M
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

80658 PLASTIC CYGLAS 620X
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005967 3

Information Handling Services, 2000

84244 PLASTIC D33
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84245 PLASTIC D44
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84246 PLASTIC D45
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84247 PLASTIC D62
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84248 PLASTIC D62CM
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84249 PLASTIC D63
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84250 PLASTIC D69
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84251 PLASTIC D72
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84252 PLASTIC D73
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84253 PLASTIC D73F
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

80541 PLASTIC DAIKIN TEFLON FEP NP30
MANF: AFTON PLASTICS
....NO TEST DATA AVAILABLE....

83731 PLASTIC DBDA0160 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

69783 PLASTIC DELRIN
MANF: CADILLAC PLASTICS

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.47	.05	.00		No test data		

68605 PLASTIC DELRIN 100
MANF: DUPONT
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005968 5 ■

Information Handling Services, 2000

68612 PLASTIC DELRIN 100AF
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68608 PLASTIC DELRIN 100CL
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68611 PLASTIC DELRIN 100D
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68606 PLASTIC DELRIN 100F
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68621 PLASTIC DELRIN 100ST
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68610 PLASTIC DELRIN 107
MANF: DUPONT
....NO TEST DATA AVAILABLE....

84421 PLASTIC DELRIN 150
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

68607 PLASTIC DELRIN 150SA
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68627 PLASTIC DELRIN 200PL
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68623 PLASTIC DELRIN 500AF
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68624 PLASTIC DELRIN 500CL
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68622 PLASTIC DELRIN 500D
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68614 PLASTIC DELRIN 500F
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68615 PLASTIC DELRIN 500HP
MANF: DUPONT
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005969 7

Information Handling Services, 2000

68628 PLASTIC DELRIN 500T
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68609 PLASTIC DELRIN 507
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68616 PLASTIC DELRIN 510AF
MANF: DUPONT
....NO TEST DATA AVAILABLE....

84422 PLASTIC DELRIN 550
MANF: CADILLAC PLASTICS

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.39	.02	.00		No test data		

68613 PLASTIC DELRIN 550SA
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68617 PLASTIC DELRIN 570
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68625 PLASTIC DELRIN 577
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68618 PLASTIC DELRIN 900
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68619 PLASTIC DELRIN 900D
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68626 PLASTIC DELRIN 900F
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68620 PLASTIC DELRIN 900HP
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68550 PLASTIC DELRIN 907F
MANF: DUPONT
....NO TEST DATA AVAILABLE....

69791 PLASTIC DELRIN AF POLYACETAL FILLED HOMO
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

84836 PLASTIC DERAKANE 411-45
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005970 3

Information Handling Services, 2000

69514 PLASTIC DERAKANE 470
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

84838 PLASTIC DERAKANE 470-36
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84839 PLASTIC DERAKANE 510A-40
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

69515 PLASTIC DERAKANE 510N
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

84840 PLASTIC DERAKANE 530
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84842 PLASTIC DERAKANE 8084
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84427 PLASTIC DEVCON WET SURFACE REPAIR PUTTY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

83728 PLASTIC DFD4960 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83729 PLASTIC DFD6005 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83730 PLASTIC DFD6201 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83732 PLASTIC DFDA0588 BLACK 9863
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83733 PLASTIC DFDA4964 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83734 PLASTIC DFDA6059 BLACK 9865
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83735 PLASTIC DFDA6080 BLACK 4865
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005971 5

Information Handling Services, 2000

83736 PLASTIC DFDA6202 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83737 PLASTIC DFDA6423 BLACK 9865
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83738 PLASTIC DFDA6425 BLACK 9865
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83739 PLASTIC DFDA7540 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83740 PLASTIC DFNF0092 BLACK
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83741 PLASTIC DGDA2400
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83742 PLASTIC DGDA2483 BLACK 4865
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83743 PLASTIC DGDA3485 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83744 PLASTIC DGDB2480 BLACK 4865
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83745 PLASTIC DGDB3110 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83746 PLASTIC DGDJ3364 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83747 PLASTIC DGDJ3479 BLACK 9865
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83754 PLASTIC DHDA2463 BLACK 4865
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83748 PLASTIC DHDA6497 BLACK 9865
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005972 7 ■

Information Handling Services, 2000

83749 PLASTIC DHDA7704 BLACK 55
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

82119 PLASTIC DIELECTRITE 44 DR-UL BMC
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82113 PLASTIC DIELECTRITE 44-0
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82114 PLASTIC DIELECTRITE 44-1 BMC
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82115 PLASTIC DIELECTRITE 44-10 BMC
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82116 PLASTIC DIELECTRITE 44-10 HG
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82117 PLASTIC DIELECTRITE 44-10 HG-C
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82118 PLASTIC DIELECTRITE 44-22 BMC
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82120 PLASTIC DIELECTRITE 46-09 BMC
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82121 PLASTIC DIELECTRITE 46-12 BMC
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82122 PLASTIC DIELECTRITE 46-14
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82123 PLASTIC DIELECTRITE 46-16 BMC
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82124 PLASTIC DIELECTRITE 46-3 BMC
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82125 PLASTIC DIELECTRITE 48-50 BMC
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005973 9

Information Handling Services, 2000

82126 PLASTIC DIELECTRITE 48-56 BMC
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

68007 PLASTIC DISPERSION 8-31B
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

84822 PLASTIC DIXON 20% GLASS 5% GRAPHITE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

84824 PLASTIC DIXON 55% BRONZE 5% MOS2
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

84826 PLASTIC DIXON 60% BRONZE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68571 PLASTIC DIXON COMPOUND 201 PTFE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68570 PLASTIC DIXON COMPOUND 7035 PTFE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

84827 PLASTIC DIXON NYLON 6/6 40% CF
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

84543 PLASTIC DK17
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84537 PLASTIC DK17-01
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.32	.64	1.16	.67H-320F-	No test data		

84544 PLASTIC DK17-05
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84538 PLASTIC DK18-05
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84539 PLASTIC DK27
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84540 PLASTIC DK28
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005974 0

Information Handling Services, 2000

84541 PLASTIC DK30
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84542 PLASTIC DK32
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

62045 PLASTIC DKE450/ACRYLIC PVC GID: DKAKAE
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.117			00.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.7E-6	.28	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.03	

69278 PLASTIC DMC
MANF: FILLITE U S A INC
....NO TEST DATA AVAILABLE....

83750 PLASTIC DMDA6010 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83751 PLASTIC DMDA6020 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83752 PLASTIC DMDA6143 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83753 PLASTIC DMDA6145 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83755 PLASTIC DMDA6147 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83756 PLASTIC DMDA7154 NATURAL 7UV
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83757 PLASTIC DMDA8920 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83758 PLASTIC DMDA8940 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83759 PLASTIC DMDA4070 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005975 2

83760 PLASTIC DNDC7148 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83761 PLASTIC DNDC7150 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

84703 PLASTIC DOLFLEX CC1015
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

84706 PLASTIC DOLPHON CB1076
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

84709 PLASTIC DOLPHON CB1078
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

84711 PLASTIC DOLPHON CB1078/RE2000
MANF: DOLPH CHEMICAL

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.09	.01	.00	720H-70F-	No test data		

84714 PLASTIC DOLPHON CB1078/RE2001
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

84715 PLASTIC DOLPHON CB1078/RE2005
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

84716 PLASTIC DOLPHON CB1078/RE2009
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

84717 PLASTIC DOLPHON CB1078/RE2010
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

84719 PLASTIC DOLPHON CB1078/RE2019
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

84722 PLASTIC DOLPHON CB1112A/CB1112B
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

84721 PLASTIC DOLPHON CB1112A/RE2000
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

84723 PLASTIC DOLPHON CB1116
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005976 4

Information Handling Services, 2000

84724 PLASTIC DOLPHON CC1079/RE2000
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

84725 PLASTIC DOLPHON CC1079/RE2005
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

84726 PLASTIC DOLPHON CC1095
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

84727 PLASTIC DOLPHON CC1106
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

84729 PLASTIC DOLPHON CR1035
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

84730 PLASTIC DOLPHON CR1050
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

83762 PLASTIC DQDA6832 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

85416 PLASTIC DRICLAD PVC NORMAL GRADE GRAY COLOR GID: DKXXXX
MANF: E P S LOGISTICS TECH

		FLAMMABILITY							FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	%REACT	%TEST
A	1	020.9	014.7	0.043		00.13	05.00	NONE	No test data		No test data							

69734 PLASTIC DUOGARD
MANF: RICHMOND
....NO TEST DATA AVAILABLE....

85339 PLASTIC DURALOY 2000
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85340 PLASTIC DURALOY 2100
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85341 PLASTIC DUREL 400
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85342 PLASTIC DUREL 410
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85343 PLASTIC DUREL 420
MANF: CELANESE
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

85344 PLASTIC DUREL 430
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85345 PLASTIC DUREL 440
MANF: CELANESE
....NO TEST DATA AVAILABLE....

68671 PLASTIC DUREZ 111
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68722 PLASTIC DUREZ 111 BLACK
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68723 PLASTIC DUREZ 111 BROWN
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68696 PLASTIC DUREZ 115
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68742 PLASTIC DUREZ 11540
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68672 PLASTIC DUREZ 118
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68724 PLASTIC DUREZ 118 BLACK
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68725 PLASTIC DUREZ 118 BROWN
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68700 PLASTIC DUREZ 123
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68726 PLASTIC DUREZ 123 BLACK
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68727 PLASTIC DUREZ 123 BROWN
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68676 PLASTIC DUREZ 13124
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005978 8 ■

Information Handling Services, 2000

68710 PLASTIC DUREZ 13856
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68744 PLASTIC DUREZ 13856AF
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68706 PLASTIC DUREZ 145
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68728 PLASTIC DUREZ 145 BLACK
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68729 PLASTIC DUREZ 145 BROWN
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68745 PLASTIC DUREZ 14900
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68679 PLASTIC DUREZ 152
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68730 PLASTIC DUREZ 152 BLACK
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68731 PLASTIC DUREZ 152 BROWN
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68704 PLASTIC DUREZ 153
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68732 PLASTIC DUREZ 153 BLACK
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68733 PLASTIC DUREZ 153 BROWN
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68680 PLASTIC DUREZ 156
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68705 PLASTIC DUREZ 157
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005979 T

68673 PLASTIC DUREZ 16038
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68735 PLASTIC DUREZ 161
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68686 PLASTIC DUREZ 16378
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68709 PLASTIC DUREZ 165
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68701 PLASTIC DUREZ 17080
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68749 PLASTIC DUREZ 17156
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68711 PLASTIC DUREZ 17702
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68750 PLASTIC DUREZ 18420
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68682 PLASTIC DUREZ 18441
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68677 PLASTIC DUREZ 18683
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68740 PLASTIC DUREZ 1898
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68698 PLASTIC DUREZ 21028
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68674 PLASTIC DUREZ 21206
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68754 PLASTIC DUREZ 21206 BLACK
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005980 6 ■

Information Handling Services, 2000

68755 PLASTIC DUREZ 21206 BROWN
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68707 PLASTIC DUREZ 21210
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68683 PLASTIC DUREZ 21372
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68702 PLASTIC DUREZ 22251
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68758 PLASTIC DUREZ 22257 BLACK
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68759 PLASTIC DUREZ 22257 BROWN
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68699 PLASTIC DUREZ 22486
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68716 PLASTIC DUREZ 22761 DAP
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68761 PLASTIC DUREZ 22787
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68688 PLASTIC DUREZ 23410
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68694 PLASTIC DUREZ 23570
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68763 PLASTIC DUREZ 24060
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68713 PLASTIC DUREZ 24150
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68689 PLASTIC DUREZ 24337
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005981 8

68714 PLASTIC DUREZ 24668
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68692 PLASTIC DUREZ 24776 DAP
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68768 PLASTIC DUREZ 24776 GRAY
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68767 PLASTIC DUREZ 24776 GREEN
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68737 PLASTIC DUREZ 265
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68769 PLASTIC DUREZ 27398
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68690 PLASTIC DUREZ 27962
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68708 PLASTIC DUREZ 28615
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68719 PLASTIC DUREZ 29053
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68678 PLASTIC DUREZ 29237
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68715 PLASTIC DUREZ 29276
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68717 PLASTIC DUREZ 29281 DAP
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

84162 PLASTIC DUREZ 29429
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68773 PLASTIC DUREZ 29502
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005982 T ■

Information Handling Services, 2000

68774 PLASTIC DUREZ 30169
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68775 PLASTIC DUREZ 30270
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68687 PLASTIC DUREZ 30417
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68776 PLASTIC DUREZ 30614 BLACK
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68777 PLASTIC DUREZ 30614 GREEN
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68778 PLASTIC DUREZ 30645
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68695 PLASTIC DUREZ 3065
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68684 PLASTIC DUREZ 30698
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68675 PLASTIC DUREZ 30725
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68712 PLASTIC DUREZ 30806
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68681 PLASTIC DUREZ 30959
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68720 PLASTIC DUREZ 31219
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68693 PLASTIC DUREZ 31375 POLY
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68718 PLASTIC DUREZ 31572 POLY
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005983 1

Information Handling Services, 2000

68703 PLASTIC DUREZ 31735
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68685 PLASTIC DUREZ 3948
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68738 PLASTIC DUREZ 740
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68697 PLASTIC DUREZ 791
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

68691 PLASTIC DUREZ S1-75 DAP
MANF: HOOKER CHEMICAL
....NO TEST DATA AVAILABLE....

67851 PLASTIC DYLARK 132
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67852 PLASTIC DYLARK 138
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67854 PLASTIC DYLARK 232
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67855 PLASTIC DYLARK 238
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67857 PLASTIC DYLARK 238 F20A
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67856 PLASTIC DYLARK 238S
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67858 PLASTIC DYLARK 238S F20A
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67859 PLASTIC DYLARK 240
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67861 PLASTIC DYLARK 250
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005984 3

Information Handling Services, 2000

67862 PLASTIC DYLARK 332
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67863 PLASTIC DYLARK 338
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67864 PLASTIC DYLARK 338S
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67865 PLASTIC DYLARK 338S F20A
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67866 PLASTIC DYLARK 350
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67853 PLASTIC DYLARK 378
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

67860 PLASTIC DYLARK 700
MANF: ARCO CHEMICAL CO
....NO TEST DATA AVAILABLE....

84156 PLASTIC DYNAMOLD DMS4-828
MANF: DYNAMOLD INC
....NO TEST DATA AVAILABLE....

84153 PLASTIC DYNAMOLD MS26
MANF: DYNAMOLD INC
....NO TEST DATA AVAILABLE....

81494 PLASTIC E20328
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81495 PLASTIC E2171 8X60
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81496 PLASTIC E2171 8X61
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81497 PLASTIC E2171 8X65
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81498 PLASTIC E260H
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005985 5

Information Handling Services, 2000

81499 PLASTIC E261H
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81500 PLASTIC E264H
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81501 PLASTIC E2748-9641CB
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

84254 PLASTIC E484
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84255 PLASTIC E486
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84256 PLASTIC E487
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84257 PLASTIC E4905
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84258 PLASTIC E4920
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84259 PLASTIC E4930
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

68532 PLASTIC E50047
MANF.: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

82127 PLASTIC E7052
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82128 PLASTIC E7074
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

81502 PLASTIC E7300
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81503 PLASTIC E8353
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F
9999942 0005986 7

Information Handling Services, 2000

81504 PLASTIC E8354
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81505 PLASTIC E8354-19189
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81506 PLASTIC E8379
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81507 PLASTIC E8382
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81508 PLASTIC E8411
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81509 PLASTIC E8414
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81510 PLASTIC E8625
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81511 PLASTIC E8636
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

85355 PLASTIC EA3000
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

85356 PLASTIC EA3100
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

85357 PLASTIC EA3200
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84199 PLASTIC EA6740
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84200 PLASTIC EA6750
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84201 PLASTIC EA6765
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005987 9

Information Handling Services, 2000

84202 PLASTIC EA9400
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84203 PLASTIC EB6780
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84204 PLASTIC EC2100
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84205 PLASTIC EC6600
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84206 PLASTIC EC6760
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84207 PLASTIC EC6770
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84429 PLASTIC ECCOFOAM PS
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.73	.00	1.24		No test data		

84430 PLASTIC ECCOGEL 1365
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84431 PLASTIC ECCOGEL 1365-12
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84432 PLASTIC ECCOGEL 1365-25
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84433 PLASTIC ECCOGEL 1365-35
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84434 PLASTIC ECCOGEL 1365-45
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84435 PLASTIC ECCOGEL 1365-65
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84436 PLASTIC ECCOGEL 1365-80
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005988 0 ■

Information Handling Services, 2000

84437 PLASTIC ECCOGEL 1365-9
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84438 PLASTIC ECCOGEL 1365-90
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84441 PLASTIC ECCOSEAL 1207
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.40	.00	.05	1H-70F- 12H-158F-

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

84443 PLASTIC ECCOSEAL W19
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.39	.34	.00	16H-171F-

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

84444 PLASTIC ECCOSEAL W28G
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84442 PLASTIC ECCOSEAL W67
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84445 PLASTIC ECCOSHIELD CLV
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84446 PLASTIC ECCOSHIELD SV
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	14.07	8.58	.00	

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

68013 PLASTIC ECTFE
MANF: CHEMPLAST
....NO TEST DATA AVAILABLE....

84545 PLASTIC EE0036/HD3561
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84546 PLASTIC EE0036/HD3615
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84547 PLASTIC EE0067/HD3404
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84548 PLASTIC EE0067/HD3561
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005989 2

84549 PLASTIC EE0067/HD3615
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84550 PLASTIC EE0149/HD3561
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84551 PLASTIC EE1067/HD3561
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84552 PLASTIC EE1068/HD0242
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84553 PLASTIC EE1068/HD0243
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84554 PLASTIC EE1087/HD3404
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84555 PLASTIC EE1087/HD3561
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84556 PLASTIC EE1087/HD3615
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84557 PLASTIC EE4143/HD3404
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84558 PLASTIC EE4143/HD3475 FILLED
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84559 PLASTIC EE4143/HD3490
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84560 PLASTIC EE4183/HD0242
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84561 PLASTIC EE4183/HD0243
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84562 PLASTIC EE4183/HD3404
MANF: HYSOL/DEXTER

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.10	.01		.5H-140F-	No test data		

MSFC-HDBK-527 REV F 9999942 0005990 9

Information Handling Services, 2000

84563 PLASTIC EE4183/HD3410
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84564 PLASTIC EE4183/HD3469
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84565 PLASTIC EE4183/HD3475 FILLED
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84566 PLASTIC EE4183/HD3485
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84567 PLASTIC EE4183/HD3490
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84568 PLASTIC EE4183/HD3537
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84569 PLASTIC EE4183/HD3561
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84570 PLASTIC EE4183/HD3615
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84571 PLASTIC EE4183/HD3719
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84572 PLASTIC EE4183/HD3840
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84573 PLASTIC EE4186/HD3537
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84574 PLASTIC EE4799/HD3596
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

69589 PLASTIC EFM
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

69587 PLASTIC EGP-S
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0005991 0 ■

84208 PLASTIC EH6600
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

69582 PLASTIC EHC
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

69584 PLASTIC EHG-S
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

84428 PLASTIC EK40
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

82448 PLASTIC ELECTRAFIL 50EC-1
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82447 PLASTIC ELECTRAFIL 50EC-2
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82450 PLASTIC ELECTRAFIL 70EC-1
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82452 PLASTIC ELECTRAFIL 75EC1
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82453 PLASTIC ELECTRAFIL 75EC3
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82455 PLASTIC ELECTRAFIL ABS1200 AF40FR
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82457 PLASTIC ELECTRAFIL G1/SS/5
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82459 PLASTIC ELECTRAFIL G100/SS/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82462 PLASTIC ELECTRAFIL G1700/SS/3/BK5658
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82464 PLASTIC ELECTRAFIL G3/10/CF/25
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0005992 2 ■

Information Handling Services, 2000

82466 PLASTIC ELECTRAFIL G50/30/CF/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82468 PLASTIC ELECTRAFIL G50/CF/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82469 PLASTIC ELECTRAFIL G50/CF/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82478 PLASTIC ELECTRAFIL G50/CF/5/SS/5
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82479 PLASTIC ELECTRAFIL G50/SS/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82480 PLASTIC ELECTRAFIL G50/SS/5/FR
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82726 PLASTIC ELECTRAFIL J1/15/CP/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82727 PLASTIC ELECTRAFIL J1/CF/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82728 PLASTIC ELECTRAFIL J1/CF/15/TF/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82729 PLASTIC ELECTRAFIL J1/CF/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82730 PLASTIC ELECTRAFIL J1/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82731 PLASTIC ELECTRAFIL J1/CF/30/TF/13/SI/2
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82732 PLASTIC ELECTRAFIL J1/CF/30/TF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82733 PLASTIC ELECTRAFIL J1/CF/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005993 4

Information Handling Services, 2000

82734 PLASTIC ELECTRAFIL J1/CF/40/VO/OD5208
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82735 PLASTIC ELECTRAFIL J1/CF/50
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82736 PLASTIC ELECTRAFIL J1/CM/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82737 PLASTIC ELECTRAFIL J1/CM/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82738 PLASTIC ELECTRAFIL J1/CP/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82740 PLASTIC ELECTRAFIL J1/CP/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82741 PLASTIC ELECTRAFIL J1/CP/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82742 PLASTIC ELECTRAFIL J100/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82743 PLASTIC ELECTRAFIL J105/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82744 PLASTIC ELECTRAFIL J1100/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82745 PLASTIC ELECTRAFIL J1105/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82750 PLASTIC ELECTRAFIL J1106/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82755 PLASTIC ELECTRAFIL J1200/CF/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82756 PLASTIC ELECTRAFIL J1200/CF/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F
9999942 0005994 6
Information Handling Services, 2000

82759 PLASTIC ELECTRAFIL J1200/SS/7/BK2089
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82760 PLASTIC ELECTRAFIL J1300/10/CF/5/SS/5
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82762 PLASTIC ELECTRAFIL J1300/CF/15/CP/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82763 PLASTIC ELECTRAFIL J1300/CF/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82765 PLASTIC ELECTRAFIL J1300/CF/20/MS/10/TF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82773 PLASTIC ELECTRAFIL J1300/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82776 PLASTIC ELECTRAFIL J1300/CF/30/TF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82778 PLASTIC ELECTRAFIL J1300/CF/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82780 PLASTIC ELECTRAFIL J1300/CF/50/HM
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82782 PLASTIC ELECTRAFIL J1300/CN/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82783 PLASTIC ELECTRAFIL J1300/CN/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82785 PLASTIC ELECTRAFIL J1400/CF/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82786 PLASTIC ELECTRAFIL J1405/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82788 PLASTIC ELECTRAFIL J1500/CF/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005995 8

Information Handling Services, 2000

82790 PLASTIC ELECTRAFIL J1500/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82792 PLASTIC ELECTRAFIL J1700/CF/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82794 PLASTIC ELECTRAFIL J1700/CF/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82796 PLASTIC ELECTRAFIL J1800/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82799 PLASTIC ELECTRAFIL J1850/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82801 PLASTIC ELECTRAFIL J3/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82804 PLASTIC ELECTRAFIL J3/CF/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82806 PLASTIC ELECTRAFIL J3/CF/50
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82807 PLASTIC ELECTRAFIL J30/CF/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82808 PLASTIC ELECTRAFIL J4/CF/30/TF/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82810 PLASTIC ELECTRAFIL J4/CF/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82812 PLASTIC ELECTRAFIL J50/CF/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82813 PLASTIC ELECTRAFIL J50/CF/10/TF/15/FR
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82814 PLASTIC ELECTRAFIL J50/CF/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005996 T

Information Handling Services, 2000

82815 PLASTIC ELECTRAFIL J50/CF/20/TF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82816 PLASTIC ELECTRAFIL J50/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82817 PLASTIC ELECTRAFIL J50/CF/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82818 PLASTIC ELECTRAFIL J50/CP/25/FR
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82820 PLASTIC ELECTRAFIL J60/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82821 PLASTIC ELECTRAFIL J60/CP/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82822 PLASTIC ELECTRAFIL J8/15/CF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82825 PLASTIC ELECTRAFIL J80/CF/10/TF/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82823 PLASTIC ELECTRAFIL JI/CF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82826 PLASTIC ELECTRAFIL SMA38/AF/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

63519 PLASTIC ELECTROSAFE GID: DUXXXX
MANF: WILSON SALES CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.012		00.13	03.60	SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
	No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.8E-6	24.58	17.40	.05	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00023.70	

85065 PLASTIC ELVAMIDE 8023
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85066 PLASTIC ELVAMIDE 8061
MANF: DUPONT
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005997 1

Information Handling Services, 2000

85068 PLASTIC ELVAMIDE 8061M
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85070 PLASTIC ELVAMIDE 8062S
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85071 PLASTIC ELVAMIDE 8063
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85072 PLASTIC ELVAMIDE 8064
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85073 PLASTIC ELVAMIDE 8066
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85075 PLASTIC ELVAX 150
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85077 PLASTIC ELVAX 240
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85079 PLASTIC ELVAX 250
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85081 PLASTIC ELVAX 260
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85082 PLASTIC ELVAX 265
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85083 PLASTIC ELVAX 350
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85085 PLASTIC ELVAX 360
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85086 PLASTIC ELVAX 40W
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85089 PLASTIC ELVAX 450
MANF: DUPONT
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0005998 3

Information Handling Services, 2000

85091 PLASTIC ELVAX 46
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85092 PLASTIC ELVAX 460
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85094 PLASTIC ELVAX 46L
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85097 PLASTIC ELVAX 470
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85099 PLASTIC ELVAX 550
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85102 PLASTIC ELVAX 560
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85105 PLASTIC ELVAX 565
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85108 PLASTIC ELVAX 650
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85111 PLASTIC ELVAX 660
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85113 PLASTIC ELVAX 670
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85116 PLASTIC ELVAX 750
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85118 PLASTIC ELVAX 760
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85120 PLASTIC ELVAX 770
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85122 PLASTIC ELVAX LDPE
MANF: DUPONT
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0005999 5

82129 PLASTIC EM7302
MANF: DIELECTRIC POLYMERS

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.48	.00	.00	.25H-275F-12H-289F-	No test data		

81257 PLASTIC EMI-X DA30
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81259 PLASTIC EMI-X DA35
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81260 PLASTIC EMI-X DA40
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81262 PLASTIC EMI-X DC1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81266 PLASTIC EMI-X EC1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81269 PLASTIC EMI-X IC1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81270 PLASTIC EMI-X MA40
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81271 PLASTIC EMI-X OC100-10
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81272 PLASTIC EMI-X PC100-10
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81273 PLASTIC EMI-X PC1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81274 PLASTIC EMI-X QC100-10
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81278 PLASTIC EMI-X QC1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81280 PLASTIC EMI-X RA30
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006000 6

81283 PLASTIC EMI-X RA35
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81284 PLASTIC EMI-X RA40
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81286 PLASTIC EMI-X RC100-10
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81287 PLASTIC EMI-X RC100-12
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81289 PLASTIC EMI-X RC1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81292 PLASTIC EMI-X WA40
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81294 PLASTIC EMI-X WC1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81296 PLASTIC EMI-X ZC1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

68010 PLASTIC EMULSION XL20
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

82505 PLASTIC ENVEX 1315
MANF: ROGERS CORP

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.03	.00	.00	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

84575 PLASTIC EO0102
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84576 PLASTIC EO0103
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84577 PLASTIC EO0104
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84578 PLASTIC EO0105
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006001 8

84580 PLASTIC EO0106
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84584 PLASTIC EO0107
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84586 PLASTIC EO0108
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84588 PLASTIC EO0109
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84590 PLASTIC EO0110
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84591 PLASTIC EO1016
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84593 PLASTIC EO1035
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84594 PLASTIC EO1038
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

81173 PLASTIC EP1200 M100
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81152 PLASTIC EP1200 M130
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81155 PLASTIC EP1200 M135
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81172 PLASTIC EP1200 M150
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81180 PLASTIC EP1200 M170
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81181 PLASTIC EP1200 M180
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006002 T ■

Information Handling Services, 2000

81184 PLASTIC EP1200 H190
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81158 PLASTIC EP1200 H300
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81159 PLASTIC EP1200 H350
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81160 PLASTIC EP1200 H400
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81162 PLASTIC EP1200 H500
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81164 PLASTIC EP1200 H600
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81167 PLASTIC EP1200 H650
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81169 PLASTIC EP1200 H670
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81187 PLASTIC EP1205
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81189 PLASTIC EP1210 H300
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81198 PLASTIC EP1215 H300
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81191 PLASTIC EP1220 H300
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81203 PLASTIC EP1230 H300
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81205 PLASTIC EP1240 H300
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006003 1

Information Handling Services, 2000

81208 PLASTIC EP1251 H300
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81210 PLASTIC EP1255 H300
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81211 PLASTIC EP1260 H300
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81214 PLASTIC EP1400
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81215 PLASTIC EP1400 H100
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81218 PLASTIC EP1400 H300
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81220 PLASTIC EP1470 H100
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81223 PLASTIC EP1470 H300
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81225 PLASTIC EP1505 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81227 PLASTIC EP1525 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81228 PLASTIC EP1548 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81231 PLASTIC EP1561 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81234 PLASTIC EP1562 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81236 PLASTIC EP1800 A/B
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006004 3 ■

Information Handling Services, 2000

81239 PLASTIC EP4200 H100
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81241 PLASTIC EP4200 H300
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81243 PLASTIC EP4213
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

84231 PLASTIC EP5182
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

84232 PLASTIC EP5282
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

81246 PLASTIC EP8200/AB
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81248 PLASTIC EP8260 H190
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

81250 PLASTIC EP8260 H350
MANF: ISOCHEM RESINS
....NO TEST DATA AVAILABLE....

68785 PLASTIC EPBGC184
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

84233 PLASTIC EPBGC78-3
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

68789 PLASTIC EPBLE70-12
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

82517 PLASTIC EPIC RESINS P6001
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82518 PLASTIC EPIC RESINS P6004
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

81733 PLASTIC EPOCAST 11B/9812
MANF: FURANE
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006005 5 ■

Information Handling Services, 2000

81734 PLASTIC EPOCAST 31B/9216
MANF: FURANE
....NO TEST DATA AVAILABLE....

81735 PLASTIC EPOCAST 31D/9216
MANF: FURANE
....NO TEST DATA AVAILABLE....

81736 PLASTIC EPOCAST 31D/927
MANF: FURANE
....NO TEST DATA AVAILABLE....

81737 PLASTIC EPOCAST 32 A/B
MANF: FURANE
....NO TEST DATA AVAILABLE....

81738 PLASTIC EPOCAST 417
MANF: FURANE

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	3.28	.01	.00	1H-212F-	No test data		

81739 PLASTIC EPOCAST 420
MANF: FURANE
....NO TEST DATA AVAILABLE....

81740 PLASTIC EPOCAST 432
MANF: FURANE
....NO TEST DATA AVAILABLE....

81741 PLASTIC EPOCAST 442
MANF: FURANE
....NO TEST DATA AVAILABLE....

81742 PLASTIC EPOCAST 443
MANF: FURANE
....NO TEST DATA AVAILABLE....

81743 PLASTIC EPOCAST 452
MANF: FURANE
....NO TEST DATA AVAILABLE....

81744 PLASTIC EPOCAST 460
MANF: FURANE
....NO TEST DATA AVAILABLE....

81745 PLASTIC EPOCAST 461
MANF: FURANE
....NO TEST DATA AVAILABLE....

81746 PLASTIC EPOCAST 471
MANF: FURANE
....NO TEST DATA AVAILABLE....

81747 PLASTIC EPOCAST 475
MANF: FURANE
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006006 7 ■

81748 PLASTIC EPOCAST 4B A/9816
MANF: FURANE
....NO TEST DATA AVAILABLE....

81749 PLASTIC EPOCAST 4D A/951
MANF: FURANE
....NO TEST DATA AVAILABLE....

81750 PLASTIC EPOCAST 4D A/9633
MANF: FURANE
....NO TEST DATA AVAILABLE....

81751 PLASTIC EPOCAST 50 A/9449
MANF: FURANE
....NO TEST DATA AVAILABLE....

81752 PLASTIC EPOCAST 50 A/946
MANF: FURANE
....NO TEST DATA AVAILABLE....

81753 PLASTIC EPOCAST 50 A/9816
MANF: FURANE
....NO TEST DATA AVAILABLE....

81754 PLASTIC EPOCAST 9 A/B
MANF: FURANE
....NO TEST DATA AVAILABLE....

82034 PLASTIC EPOLITE 3300
MANF: HEXCEL
....NO TEST DATA AVAILABLE....

82035 PLASTIC EPOLITE 3301
MANF: HEXCEL
....NO TEST DATA AVAILABLE....

82036 PLASTIC EPOLITE 3302
MANF: HEXCEL
....NO TEST DATA AVAILABLE....

82037 PLASTIC EPOLITE 3306
MANF: HEXCEL
....NO TEST DATA AVAILABLE....

82038 PLASTIC EPOLITE 3306-1
MANF: HEXCEL
....NO TEST DATA AVAILABLE....

82039 PLASTIC EPOLITE 3354
MANF: HEXCEL
....NO TEST DATA AVAILABLE....

82040 PLASTIC EPOLITE 3362
MANF: HEXCEL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006007 9 ■

Information Handling Services, 2000

68784 PLASTIC EPSG154
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

68780 PLASTIC EPSL142
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

84234 PLASTIC EPSL166
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

84235 PLASTIC EPSL174
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

68779 PLASTIC EPSL186
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

81432 PLASTIC EPSL199
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

81433 PLASTIC EPSL201
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

81434 PLASTIC EPSL202
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

81435 PLASTIC EPSL203
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

68788 PLASTIC EPSL208
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

68783 PLASTIC EPSL213
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

68782 PLASTIC EPSL218-1
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

68781 PLASTIC EPSLE114-1
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

68787 PLASTIC EPSLE174
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006008 0

68786 PLASTIC EPSLE211
MANF: EAGLE-PICHER IND
....NO TEST DATA AVAILABLE....

68500 PLASTIC EPSYN 2506
MANF: COPOLYMER RUBBER AND CHEM CORP
....NO TEST DATA AVAILABLE....

68499 PLASTIC EPSYN 40A
MANF: COPOLYMER RUBBER AND CHEM CORP
....NO TEST DATA AVAILABLE....

68478 PLASTIC EPSYN 4506
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68501 PLASTIC EPSYN 4906
MANF: COPOLYMER RUBBER AND CHEM CORP
....NO TEST DATA AVAILABLE....

68496 PLASTIC EPSYN 5508
MANF: COPOLYMER RUBBER AND CHEM CORP
....NO TEST DATA AVAILABLE....

68396 PLASTIC EPSYN 70A
MANF: COPOLYMER RUBBER AND CHEM CORP
....NO TEST DATA AVAILABLE....

68497 PLASTIC EPSYN 7506
MANF: COPOLYMER RUBBER AND CHEM CORP
....NO TEST DATA AVAILABLE....

81696 PLASTIC ER2020
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81697 PLASTIC ER2023
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81698 PLASTIC ER2027
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81699 PLASTIC ER2028
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81700 PLASTIC ER2036
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81702 PLASTIC ER2047
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006009 2

Information Handling Services, 2000

81703 PLASTIC ER2205
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81704 PLASTIC ER2220
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81705 PLASTIC ER2300
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81706 PLASTIC ER2380
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81707 PLASTIC ER2381
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81708 PLASTIC ER2400
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

81701 PLASTIC ER3042
MANF: FORMULATED RESINS
....NO TEST DATA AVAILABLE....

84598 PLASTIC ES0002
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84599 PLASTIC ES0007
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84600 PLASTIC ES0032
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84604 PLASTIC ES0033
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84606 PLASTIC ES0042
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84607 PLASTIC ES0043
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84608 PLASTIC ES0047
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006010 9 ■

Information Handling Services, 2000

84609 PLASTIC ES0052
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84610 PLASTIC ES0269
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84611 PLASTIC ES0329
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

68453 PLASTIC ES20GF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68455 PLASTIC ES30CF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68479 PLASTIC ES39GF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68454 PLASTIC ES40GF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

84612 PLASTIC ES4212
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84613 PLASTIC ES4312
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84614 PLASTIC ES4322
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84615 PLASTIC ES4323
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84616 PLASTIC ES4325
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84617 PLASTIC ES4326
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84596 PLASTIC ES4412
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006011 0 ■

Information Handling Services, 2000

81094 PLASTIC ES6040
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

81095 PLASTIC ES6060
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

81096 PLASTIC ES6071
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

81098 PLASTIC ES6072
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

81099 PLASTIC ES6360
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

81101 PLASTIC ES6461
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

81102 PLASTIC ES6477
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

81104 PLASTIC ES666
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

68480 PLASTIC ES7CF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

69591 PLASTIC ESA-S
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

81492 PLASTIC ESCORENE
MANF: EXXON
....NO TEST DATA AVAILABLE....

68921 PLASTIC ESCORENE 1012
MANF: EXXON
....NO TEST DATA AVAILABLE....

68923 PLASTIC ESCORENE 1024
MANF: EXXON
....NO TEST DATA AVAILABLE....

68927 PLASTIC ESCORENE 1032
MANF: EXXON
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV.F 9999942 0006012 2

Information Handling Services, 2000

68925 PLASTIC ESCORENE 1042
MANF: EXXON
....NO TEST DATA AVAILABLE....

81493 PLASTIC ESCORENE 1044
MANF: EXXON
....NO TEST DATA AVAILABLE....

68926 PLASTIC ESCORENE 1052
MANF: EXXON
....NO TEST DATA AVAILABLE....

68922 PLASTIC ESCORENE 1063
MANF: EXXON
....NO TEST DATA AVAILABLE....

68924 PLASTIC ESCORENE 1074
MANF: EXXON
....NO TEST DATA AVAILABLE....

68931 PLASTIC ESCORENE 1105
MANF: EXXON
....NO TEST DATA AVAILABLE....

68929 PLASTIC ESCORENE 1154
MANF: EXXON
....NO TEST DATA AVAILABLE....

68930 PLASTIC ESCORENE 1164
MANF: EXXON
....NO TEST DATA AVAILABLE....

68928 PLASTIC ESCORENE 1172
MANF: EXXON
....NO TEST DATA AVAILABLE....

68932 PLASTIC ESCORENE 1222F
MANF: EXXON
....NO TEST DATA AVAILABLE....

68934 PLASTIC ESCORENE 1224F
MANF: EXXON
....NO TEST DATA AVAILABLE....

68933 PLASTIC ESCORENE 1403F
MANF: EXXON
....NO TEST DATA AVAILABLE....

68935 PLASTIC ESCORENE 1404F
MANF: EXXON
....NO TEST DATA AVAILABLE....

68946 PLASTIC ESCORENE 2072
MANF: EXXON
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006013 4 ■

Information Handling Services, 2000

68947 PLASTIC ESCORENE 2082
MANF: EXXON
....NO TEST DATA AVAILABLE....

68948 PLASTIC ESCORENE 2092
MANF: EXXON
....NO TEST DATA AVAILABLE....

68949 PLASTIC ESCORENE 3014
MANF: EXXON
....NO TEST DATA AVAILABLE....

68951 PLASTIC ESCORENE 3035
MANF: EXXON
....NO TEST DATA AVAILABLE....

68953 PLASTIC ESCORENE 3045
MANF: EXXON
....NO TEST DATA AVAILABLE....

81086 PLASTIC ESCORENE 3114G
MANF: EXXON
....NO TEST DATA AVAILABLE....

68954 PLASTIC ESCORENE 3125
MANF: EXXON
....NO TEST DATA AVAILABLE....

68955 PLASTIC ESCORENE 3145
MANF: EXXON
....NO TEST DATA AVAILABLE....

68952 PLASTIC ESCORENE 3235
MANF: EXXON
....NO TEST DATA AVAILABLE....

68950 PLASTIC ESCORENE 3274
MANF: EXXON
....NO TEST DATA AVAILABLE....

68941 PLASTIC ESCORENE 4023
MANF: EXXON
....NO TEST DATA AVAILABLE....

68943 PLASTIC ESCORENE 4033
MANF: EXXON
....NO TEST DATA AVAILABLE....

68939 PLASTIC ESCORENE 4062
MANF: EXXON
....NO TEST DATA AVAILABLE....

68940 PLASTIC ESCORENE 4082
MANF: EXXON
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F
9999942 0006014 6

Information Handling Services, 2000

68938 PLASTIC ESCORENE 4092
MANF: EXXON
....NO TEST DATA AVAILABLE....

68944 PLASTIC ESCORENE 4103
MANF: EXXON
....NO TEST DATA AVAILABLE....

68945 PLASTIC ESCORENE 4134
MANF: EXXON
....NO TEST DATA AVAILABLE....

68936 PLASTIC ESCORENE 4152
MANF: EXXON
....NO TEST DATA AVAILABLE....

68937 PLASTIC ESCORENE 4162
MANF: EXXON
....NO TEST DATA AVAILABLE....

68942 PLASTIC ESCORENE 4193
MANF: EXXON
....NO TEST DATA AVAILABLE....

68958 PLASTIC ESCORENE 5022
MANF: EXXON
....NO TEST DATA AVAILABLE....

68957 PLASTIC ESCORENE 5052
MANF: EXXON
....NO TEST DATA AVAILABLE....

81089 PLASTIC ESCORENE 5141G
MANF: EXXON
....NO TEST DATA AVAILABLE....

81092 PLASTIC ESCORENE 5164G
MANF: EXXON
....NO TEST DATA AVAILABLE....

68956 PLASTIC ESCORENE 5181
MANF: EXXON
....NO TEST DATA AVAILABLE....

68967 PLASTIC ESCORENE 7022
MANF: EXXON
....NO TEST DATA AVAILABLE....

68966 PLASTIC ESCORENE 7032
MANF: EXXON
....NO TEST DATA AVAILABLE....

68968 PLASTIC ESCORENE 7033
MANF: EXXON
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006015 8 ■

Information Handling Services, 2000

68969 PLASTIC ESCORENE 7034
MANF: EXXON
....NO TEST DATA AVAILABLE....

68964 PLASTIC ESCORENE 8032
MANF: EXXON
....NO TEST DATA AVAILABLE....

68965 PLASTIC ESCORENE 8042
MANF: EXXON
....NO TEST DATA AVAILABLE....

68963 PLASTIC ESCORENE 8051
MANF: EXXON
....NO TEST DATA AVAILABLE....

68961 PLASTIC ESCORENE 9012
MANF: EXXON
....NO TEST DATA AVAILABLE....

68960 PLASTIC ESCORENE 9022
MANF: EXXON
....NO TEST DATA AVAILABLE....

68959 PLASTIC ESCORENE 9032
MANF: EXXON
....NO TEST DATA AVAILABLE....

68962 PLASTIC ESCORENE 9044
MANF: EXXON
....NO TEST DATA AVAILABLE....

81097 PLASTIC ESCORENE LD-701
MANF: EXXON
....NO TEST DATA AVAILABLE....

81100 PLASTIC ESCORENE LD-702
MANF: EXXON
....NO TEST DATA AVAILABLE....

69590 PLASTIC ESG-S
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

80529 PLASTIC ESTRALON PET
MANF: AEROMAT PLASTICS
....NO TEST DATA AVAILABLE....

68012 PLASTIC ETFE
MANF: CHEMPLAST
....NO TEST DATA AVAILABLE....

82828 PLASTIC ETHOFIL G90/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006016 T ■

Information Handling Services, 2000

82830 PLASTIC ETHOFIL G90/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82831 PLASTIC ETHOFIL J90/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82833 PLASTIC ETHOFIL J90/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

69586 PLASTIC ETR-FR-C
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

69581 PLASTIC ETS
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

69585 PLASTIC ETS-FR
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

69583 PLASTIC ETS-FR-11
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

68530 PLASTIC EXOLITE DOUBLE SKINNED ACRYLIC SHEET
MANF: CY/RO INDUSTRIES
....NO TEST DATA AVAILABLE....

68531 PLASTIC EXOLITE DOUBLE SKINNED POLYCARBONATE SHEET
MANF: CY/RO INDUSTRIES
....NO TEST DATA AVAILABLE....

67867 PLASTIC EZ-CAST 521 PLASTIC MOLDING COMPOUND
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

67868 PLASTIC EZ-CAST 588 PLASTIC MOLDING COMPOUND
MANF: AREMCO PRODUCTS
....NO TEST DATA AVAILABLE....

67344 PLASTIC F18 R/H
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67341 PLASTIC F180R/F181H
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

84077 PLASTIC FASTOOL RP3265
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006017 1 ■

82835 PLASTIC FIBERFIL G2/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82838 PLASTIC FIBERFIL G2/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82839 PLASTIC FIBERFIL G2/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82841 PLASTIC FIBERFIL G2/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82842 PLASTIC FIBERFIL J1105/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82844 PLASTIC FIBERFIL J1106/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82845 PLASTIC FIBERFIL J1106/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82847 PLASTIC FIBERFIL J11106/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82852 PLASTIC FIBERFIL J1300/25/MF/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82864 PLASTIC FIBERFIL J1700/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82851 PLASTIC FIBERFIL J1700/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82855 PLASTIC FIBERFIL J1700/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82856 PLASTIC FIBERFIL J2/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82857 PLASTIC FIBERFIL J2/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006018 3 ■

Information Handling Services, 2000

82859 PLASTIC FIBERFIL J2/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82861 PLASTIC FIBERFIL J2/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

69280 PLASTIC FILLITE 100/7
MANF: FILLITE U S A INC
....NO TEST DATA AVAILABLE....

69279 PLASTIC FILLITE 200/7
MANF: FILLITE U S A INC
....NO TEST DATA AVAILABLE....

69282 PLASTIC FILLITE 300/7
MANF: FILLITE U S A INC
....NO TEST DATA AVAILABLE....

69281 PLASTIC FILLITE 52/7/5
MANF: FILLITE U S A INC
....NO TEST DATA AVAILABLE....

69286 PLASTIC FILLITE IN POLYESTER RESIN
MANF: FILLITE U S A INC
....NO TEST DATA AVAILABLE....

69285 PLASTIC FILLITE M32
MANF: FILLITE U S A INC
....NO TEST DATA AVAILABLE....

69287 PLASTIC FILLITE MICRO BALLONS
MANF: FILLITE U S A INC
....NO TEST DATA AVAILABLE....

69288 PLASTIC FILLITE MICRO BALLONS IN EPOXY RESINS
MANF: FILLITE U S A INC
....NO TEST DATA AVAILABLE....

69284 PLASTIC FILLITE P2000
MANF: FILLITE U S A INC
....NO TEST DATA AVAILABLE....

69283 PLASTIC FILLITE PFA
MANF: FILLITE U S A INC
....NO TEST DATA AVAILABLE....

69761 PLASTIC FLEXANE 80 LIQUID
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

69762 PLASTIC FLEXANE 94 LIQUID
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006019 5

Information Handling Services, 2000

69765 PLASTIC FLEXANE BRUSHABLE URETHANE
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

69764 PLASTIC FLEXANE HIGH PERFORMANCE PUTTY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

69763 PLASTIC FLEXANE PUTTY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

69759 PLASTIC FLOOR GRIP
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

69760 PLASTIC FLOOR PATCH
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

69562 PLASTIC FLOUROSINT 207
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69561 PLASTIC FLOUROSINT 500
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69560 PLASTIC FLOUROSINT TFE
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69906 PLASTIC FLUOROCARBON WAFER
MANF: FLUOROCARBON CORP

FLAMMABILITY							FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	14.7	72	-297	0.020	00	20

69295 PLASTIC FLUOROGOLD
MANF: FLUOROCARBON CORP
....NO TEST DATA AVAILABLE....

69292 PLASTIC FLUOROLOY A
MANF: FLUOROCARBON CORP
....NO TEST DATA AVAILABLE....

69289 PLASTIC FLUOROLOY C
MANF: FLUOROCARBON CORP
....NO TEST DATA AVAILABLE....

69293 PLASTIC FLUOROLOY G
MANF: FLUOROCARBON CORP
....NO TEST DATA AVAILABLE....

69290 PLASTIC FLUOROLOY X
MANF: FLUOROCARBON CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006020 1

69294 PLASTIC FLUOROLOY Y
MANF: FLUOROCARBON CORP
....NO TEST DATA AVAILABLE....

69291 PLASTIC FLUOROLOY Z
MANF: FLUOROCARBON CORP
....NO TEST DATA AVAILABLE....

81298 PLASTIC FLUOROMELT FPCC1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81301 PLASTIC FLUOROMELT FPCF1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81302 PLASTIC FLUOROMELT FPCF1006
MANF: L N P CORP

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.10	.01	.00	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

81306 PLASTIC FLUOROMELT FPCL4020
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81303 PLASTIC FLUOROMELT FPCLF4024
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81308 PLASTIC FLUOROMELT FPEC1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81310 PLASTIC FLUOROMELT FPEC1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81317 PLASTIC FLUOROMELT FPEEL4024
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81313 PLASTIC FLUOROMELT FPEF1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81315 PLASTIC FLUOROMELT FPEF1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81320 PLASTIC FLUOROMELT FPEL4060
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81322 PLASTIC FLUOROMELT FPFC1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006021 3

81325 PLASTIC FLUOROMELT FPFF1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81328 PLASTIC FLUOROMELT FPFF1004M
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81330 PLASTIC FLUOROMELT FPFL4020
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81333 PLASTIC FLUOROMELT FPPC1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81336 PLASTIC FLUOROMELT FPPCL4024
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81338 PLASTIC FLUOROMELT FPPF1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81340 PLASTIC FLUOROMELT FPPF1004M
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81341 PLASTIC FLUOROMELT FPPL4020
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81343 PLASTIC FLUOROMELT FPVC1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81345 PLASTIC FLUOROMELT FPVCL4024
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81346 PLASTIC FLUOROMELT FPVM2550
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81347 PLASTIC FLUOROMELT FPVM3830
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81349 PLASTIC FLUOROMELT FPVM3850
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81685 PLASTIC FLUOROTEMP 103
MANF: FLUOROCARBON CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006022 5 ■

81512 PLASTIC FM10365
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81513 PLASTIC FM1303-8880
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81514 PLASTIC FM16771
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81515 PLASTIC FM21288
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81516 PLASTIC FM3000
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81517 PLASTIC FM3001
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81518 PLASTIC FM3002
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81519 PLASTIC FM32168
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81520 PLASTIC FM32175
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81521 PLASTIC FM32780
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81522 PLASTIC FM3510
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81523 PLASTIC FM4002
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81524 PLASTIC FM4004
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81526 PLASTIC FM4005 X 4648
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006023 7

Information Handling Services, 2000

81525 PLASTIC FM4005F
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81527 PLASTIC FM4007
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81528 PLASTIC FM4009
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81529 PLASTIC FM4011
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81530 PLASTIC FM4024
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81531 PLASTIC FM4029F
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81532 PLASTIC FM4036
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81533 PLASTIC FM4055
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81534 PLASTIC FM4056
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81535 PLASTIC FM4060
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81536 PLASTIC FM4070
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81537 PLASTIC FM4555
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81538 PLASTIC FM50501
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81539 PLASTIC FM5064
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006024 9 ■

Information Handling Services, 2000

81540 PLASTIC FM5085
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81541 PLASTIC FM510
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81542 PLASTIC FM5367
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81543 PLASTIC FM6030
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81544 PLASTIC FM8130E
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81652 PLASTIC FM8720
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81653 PLASTIC FM9294
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

69218 PLASTIC FOAMABLE TENITE POLYPROPYLENE P2635-08AA
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69519 PLASTIC FOAMEX
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

80778 PLASTIC FORAFLON 1000HD
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

82867 PLASTIC FORMALDAFIL AC80/TF/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82868 PLASTIC FORMALDAFIL AC80/TF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82871 PLASTIC FORMALDAFIL AC80/TF/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82873 PLASTIC FORMALDAFIL J80/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006025 0

Information Handling Services, 2000

82875 PLASTIC FORMALDAFIL J80/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82880 PLASTIC FORMALDAFIL J80/20/TF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82883 PLASTIC FORMALDAFIL J80/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82885 PLASTIC FORMALDAFIL J80/30/TF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82888 PLASTIC FORMALDAFIL J82/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82890 PLASTIC FORMALDAFIL J82/25
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82893 PLASTIC FORMALDAFIL J82/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

80319 PLASTIC FORMION FI105
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80320 PLASTIC FORMION FI107
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80321 PLASTIC FORMION FI120
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80322 PLASTIC FORMION FI139
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80323 PLASTIC FORMION FI147
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80324 PLASTIC FORMION FI217
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80325 PLASTIC FORMION FI241
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006026 2 ■

Information Handling Services, 2000

80326 PLASTIC FORMION FI280
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

82863 PLASTIC FORTIFLEX A6070119
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82902 PLASTIC FORTIFLEX B3514F
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82869 PLASTIC FORTIFLEX B35150134
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82872 PLASTIC FORTIFLEX B4506R09
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82876 PLASTIC FORTIFLEX B5020H
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82879 PLASTIC FORTIFLEX B5035H
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82882 PLASTIC FORTIFLEX B5335H
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82887 PLASTIC FORTIFLEX B5335H100
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82892 PLASTIC FORTIFLEX B5335H126
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82895 PLASTIC FORTIFLEX B5425H
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82897 PLASTIC FORTIFLEX B5425H124
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82899 PLASTIC FORTIFLEX B5425H127
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82905 PLASTIC FORTIFLEX F444A
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006027 4

Information Handling Services, 2000

82908 PLASTIC FORTIFLEX F469A
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82912 PLASTIC FORTIFLEX F622
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82916 PLASTIC FORTIFLEX G6025119
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82918 PLASTIC FORTIFLEX G6080F
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82920 PLASTIC FORTIFLEX J60100130
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82922 PLASTIC FORTIFLEX K3411121
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82924 PLASTIC FORTIFLEX K3655123
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82926 PLASTIC FORTIFLEX K3820137
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82929 PLASTIC FORTIFLEX K4411128
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82936 PLASTIC FORTIFLEX K4415123
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82940 PLASTIC FORTIFLEX K4424123
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82943 PLASTIC FORTIFLEX K5030135
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82946 PLASTIC FORTIFLEX T353500129
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82949 PLASTIC FORTIFLEX T35600
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006028 6 ■

82952 PLASTIC FORTIFLEX T491000129
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82955 PLASTIC FORTIFLEX T501000
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82958 PLASTIC FORTIFLEX T50200
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82962 PLASTIC FORTIFLEX T502000
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82965 PLASTIC FORTIFLEX T503600119
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82967 PLASTIC FORTIFLEX T504400119
MANF: SOLEX
....NO TEST DATA AVAILABLE....

82970 PLASTIC FORTIFLEX T50500
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82977 PLASTIC FORTIFLEX T505500119
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82981 PLASTIC FORTIFLEX T601500
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82983 PLASTIC FORTIFLEX T603000119
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82987 PLASTIC FORTIFLEX T604200119
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82988 PLASTIC FORTIFLEX T60500
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82990 PLASTIC FORTIFLEX T60800
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82992 PLASTIC FORTIFLEX XF337G
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006029 8

Information Handling Services, 2000

82993 PLASTIC FORTIFLEX XF397D
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

82999 PLASTIC FORTIFLEX XF409
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83002 PLASTIC FORTIFLEX XF448
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83003 PLASTIC FORTIFLEX XF451
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83006 PLASTIC FORTIFLEX XF455
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83009 PLASTIC FORTIFLEX XF470
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83011 PLASTIC FORTIFLEX XF480A
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83013 PLASTIC FORTIFLEX XF528B
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83015 PLASTIC FORTIFLEX XF591H
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83019 PLASTIC FORTIFLEX XF600
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83024 PLASTIC FORTIFLEX XF621
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83030 PLASTIC FORTILENE 10 X 03
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83026 PLASTIC FORTILENE 1001
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83033 PLASTIC FORTILENE 1401
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006030 4

Information Handling Services, 2000

83036 PLASTIC FORTILENE 1420
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83040 PLASTIC FORTILENE 1602
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83043 PLASTIC FORTILENE 1602A
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83045 PLASTIC FORTILENE 1604
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83052 PLASTIC FORTILENE 1802
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83061 PLASTIC FORTILENE 1803
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83062 PLASTIC FORTILENE 1804
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83067 PLASTIC FORTILENE 1805
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83069 PLASTIC FORTILENE 1902
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83071 PLASTIC FORTILENE 1903
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83075 PLASTIC FORTILENE 21 X 04
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83082 PLASTIC FORTILENE 22 X 02
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83078 PLASTIC FORTILENE 2251
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83083 PLASTIC FORTILENE 3151
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006031 6 ■

Information Handling Services, 2000

83085 PLASTIC FORTILENE 3251
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83086 PLASTIC FORTILENE 3606
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83087 PLASTIC FORTILENE 3651
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83088 PLASTIC FORTILENE 3807
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83090 PLASTIC FORTILENE 39 X 09
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83089 PLASTIC FORTILENE 3907
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83091 PLASTIC FORTILENE 40 X 05
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83096 PLASTIC FORTILENE 41 X 03
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83097 PLASTIC FORTILENE 41 X 11
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83092 PLASTIC FORTILENE 4104
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83093 PLASTIC FORTILENE 4109
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83094 PLASTIC FORTILENE 4110
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83095 PLASTIC FORTILENE 4141
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83098 PLASTIC FORTILENE 4207
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006032 8 ■

Information Handling Services, 2000

83099 PLASTIC FORTILENE 4208
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83100 PLASTIC FORTILENE 4306
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83101 PLASTIC FORTILENE 45 X 02
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83102 PLASTIC FORTILENE 5402
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83105 PLASTIC FORTILENE 90 X 02
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83103 PLASTIC FORTILENE 9000
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83104 PLASTIC FORTILENE 9005
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83106 PLASTIC FORTILENE 9101
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83107 PLASTIC FORTILENE 9200
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83108 PLASTIC FORTILENE 9205
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83109 PLASTIC FORTILENE 9226
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83110 PLASTIC FORTILENE 9600
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83111 PLASTIC FORTILENE 9605
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

83112 PLASTIC FORTILENE 9625
MANF: SOLTEX
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006033 T

69396 PLASTIC FREEFLO 49-0301
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

81105 PLASTIC FS8160
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

81106 PLASTIC FS8273
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

81108 PLASTIC FS8273-70
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

81109 PLASTIC FS8476
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

81112 PLASTIC FS8477
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

81111 PLASTIC FS8490
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

81114 PLASTIC FS8575
MANF: LORD CORP
....NO TEST DATA AVAILABLE....

81351 PLASTIC FULTON 404
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.52	.01	.00		No test data		

83763 PLASTIC G RESIN 7144 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83764 PLASTIC G RESIN 7342 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83765 PLASTIC G RESIN 7441 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83766 PLASTIC G RESIN 8007 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83767 PLASTIC G RESIN 8320 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006034 1

Information Handling Services, 2000

83768 PLASTIC G RESIN 8940 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

67897 PLASTIC GEIB 8815
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67914 PLASTIC GEON 2042
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67894 PLASTIC GEON 82024
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67900 PLASTIC GEON 82611
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67899 PLASTIC GEON 83008
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67913 PLASTIC GEON 83332
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67906 PLASTIC GEON 83421
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67904 PLASTIC GEON 83457
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67912 PLASTIC GEON 83463
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67921 PLASTIC GEON 83528
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67918 PLASTIC GEON 83700
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67902 PLASTIC GEON 83718
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67901 PLASTIC GEON 83741
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006035 3

Information Handling Services, 2000

67911 PLASTIC GEON 83791
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67903 PLASTIC GEON 83794
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67920 PLASTIC GEON 86054
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67916 PLASTIC GEON 86135
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67915 PLASTIC GEON 86143
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67917 PLASTIC GEON 86144
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67907 PLASTIC GEON 86153
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67908 PLASTIC GEON 86154
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67909 PLASTIC GEON 86155
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67919 PLASTIC GEON 86188
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

68015 PLASTIC GEON 87237
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

68016 PLASTIC GEON 87239
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

68024 PLASTIC GEON 87321
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

68018 PLASTIC GEON 87341
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006036 5

Information Handling Services, 2000

68019 PLASTIC GEON 87342
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

67922 PLASTIC GEON 8804FR
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67895 PLASTIC GEON 8812
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67896 PLASTIC GEON 8813
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67898 PLASTIC GEON 8814
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67910 PLASTIC GEON 8857
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67905 PLASTIC GEON 8883
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67934 PLASTIC GEON CIM 85856
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67923 PLASTIC GEON CIM 87240
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67924 PLASTIC GEON CIM 87241
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67930 PLASTIC GEON CIM 87242
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67931 PLASTIC GEON CIM 87300
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67925 PLASTIC GEON CIM 87302
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67926 PLASTIC GEON CIM 87317
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006037 7

67932 PLASTIC GEON CIM 87319
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67929 PLASTIC GEON CIM 87322
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67927 PLASTIC GEON CIM 87366
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67928 PLASTIC GEON CIM 87371
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

67933 PLASTIC GEON CIM 87380
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

80530 PLASTIC GLASBORD S
MANF: AEROMAT PLASTICS
....NO TEST DATA AVAILABLE....

67788 PLASTIC GLASKYD 1901
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

67789 PLASTIC GLASKYD 1902
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

67790 PLASTIC GLASKYD 1910
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

67791 PLASTIC GLASKYD 2201
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

67792 PLASTIC GLASKYD 3001H
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

67793 PLASTIC GLASKYD 4000
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

67794 PLASTIC GLASKYD 4001
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

67795 PLASTIC GLASKYD 4002
MANF: AMERICAN CYANAMID
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006038 9

Information Handling Services, 2000

81832 PLASTIC GLASROD NIR
MANF: GLASTIC
....NO TEST DATA AVAILABLE....

81833 PLASTIC GLASROD MTS
MANF: GLASTIC
....NO TEST DATA AVAILABLE....

81834 PLASTIC GLASROD SG200
MANF: GLASTIC
....NO TEST DATA AVAILABLE....

81835 PLASTIC GLASTIC GPO3
MANF: GLASTIC
....NO TEST DATA AVAILABLE....

83769 PLASTIC GPEP1000
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83770 PLASTIC GPEP703 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83771 PLASTIC GPEP705 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83772 PLASTIC GPEP803 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83773 PLASTIC GPEP805 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83774 PLASTIC GPEP903 BLACK
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83775 PLASTIC GPEP954 NATURAL 7UV
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83776 PLASTIC GPSC2704 BLACK
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

69268 PLASTIC GRILAMID L16GM
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

81461 PLASTIC GRILAMID L20G
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006039 0

Information Handling Services, 2000

81462 PLASTIC GRILAMID L20W20
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

81463 PLASTIC GRILAMID L20W40
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

81464 PLASTIC GRILAMID L25
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

81465 PLASTIC GRILAMID L25W40
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69273 PLASTIC GRILAMID L25W40NZ NYLON 12
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

81466 PLASTIC GRILAMID LKN5H
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

81467 PLASTIC GRILAMID LV3H
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69269 PLASTIC GRILAMID LV43H
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69271 PLASTIC GRILAMID TR55
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69272 PLASTIC GRILAMID TR55LX
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69276 PLASTIC GRILAMID TR55UV
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69274 PLASTIC GRILAMID W2291 NYLON 12
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69270 PLASTIC GRILAMID W5941
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69275 PLASTIC GRILAMID W6923
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006040 7 ■

Information Handling Services, 2000

NON-METALS BY DESIGNATION

69254 PLASTIC GRILAM A28GM
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

81468 PLASTIC GRILON A23G NAT 6165
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

81469 PLASTIC GRILON A23GM
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

81470 PLASTIC GRILON A28GM
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69261 PLASTIC GRILON A28NX
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69255 PLASTIC GRILON A28NY
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69262 PLASTIC GRILON A28NZ
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69256 PLASTIC GRILON A28VO
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69263 PLASTIC GRILON BT40
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69257 PLASTIC GRILON CA6E
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69264 PLASTIC GRILON CR9
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

81471 PLASTIC GRILON F40
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

81472 PLASTIC GRILON F47
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

81473 PLASTIC.GRILON F50
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

69258 PLASTIC GRILON PV3H
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69259 PLASTIC GRILON PVM154
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69265 PLASTIC GRILON PVM3H
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

81474 PLASTIC GRILON R40
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

81475 PLASTIC GRILON R40GM
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69266 PLASTIC GRILON R47HW
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69260 PLASTIC GRILON W3941
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

69267 PLASTIC GRILON W5744
MANF: EMSER INDUSTRIES
....NO TEST DATA AVAILABLE....

83777 PLASTIC GRSM1077 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83778 PLASTIC GRSM7147 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83779 PLASTIC GRSM7149 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83780 PLASTIC GRSM7340 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83781 PLASTIC GRSM7341 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83782 PLASTIC GRSM7510 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006042 0 ■

Information Handling Services, 2000

83783 PLASTIC GRSM8350 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83784 PLASTIC GRSM8907 NATURAL 7
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

68649 PLASTIC GRZ 70G13 HS1L
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85124 PLASTIC GRZ 70G13 HS1L
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68648 PLASTIC GRZ 70G13L
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68650 PLASTIC GRZ 70G33 HRL
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85125 PLASTIC GRZ 70G33 HS1L
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68659 PLASTIC GRZ 70G33 HS1L 70G43L
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68658 PLASTIC GRZ 70G33L
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85127 PLASTIC GRZ 70G43L
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68651 PLASTIC GRZ 71G13L
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68660 PLASTIC GRZ 71G33L
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68656 PLASTIC GRZ 77G33L
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68661 PLASTIC GRZ 77G43L
MANF: DUPONT
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006043 2

Information Handling Services, 2000

68657 PLASTIC GRZ 80G33HS1L
MANF: DUPONT
....NO TEST DATA AVAILABLE....

80779 PLASTIC GSMR02
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

81885 PLASTIC GTC160
MANF: GREENE TWEED CO
....NO TEST DATA AVAILABLE....

69592 PLASTIC H755
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

67768 PLASTIC HALAR 500
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67769 PLASTIC HALAR 510
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

80833 PLASTIC HALAR FEP
MANF: AUSIMONT
....NO TEST DATA AVAILABLE....

67764 PLASTIC HALAR FLOUROPOLYMER
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

80834 PLASTIC HALAR PTFE
MANF: AUSIMONT
....NO TEST DATA AVAILABLE....

80835 PLASTIC HALAR PVF2
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

80604 PLASTIC HALON TFE G18
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

80605 PLASTIC HALON TFE G700
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

80606 PLASTIC HALON TFE G80
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

80608 PLASTIC HALON TFE G83
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006044 4

Information Handling Services, 2000

82005 PLASTIC HAYSITE 12000
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82006 PLASTIC HAYSITE 13600
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82007 PLASTIC HAYSITE 14100
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82008 PLASTIC HAYSITE 16100
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82009 PLASTIC HAYSITE 16600
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82010 PLASTIC HAYSITE 17000
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82011 PLASTIC HAYSITE 18500
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82012 PLASTIC HAYSITE 20000
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82013 PLASTIC HAYSITE 270 FR2
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82014 PLASTIC HAYSITE 30000
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82015 PLASTIC HAYSITE 40000
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82016 PLASTIC HAYSITE 42000
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82017 PLASTIC HAYSITE 43000
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82018 PLASTIC HAYSITE 44000
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006045 6 ■

Information Handling Services, 2000

82019 PLASTIC HAYSITE 46000
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82020 PLASTIC HAYSITE 47000
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82021 PLASTIC HAYSITE 48000
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82022 PLASTIC HAYSITE 53000
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82023 PLASTIC HAYSITE 60000
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82024 PLASTIC HAYSITE 70000
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

84792 PLASTIC HDPE 25050P
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84791 PLASTIC HDPE 25053P
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84794 PLASTIC HDPE 69065P
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

83785 PLASTIC HFDA0580 BLACK 55
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83786 PLASTIC HFDA0581 BLACK 55
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83787 PLASTIC HFDA0691 BLACK 55
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83788 PLASTIC HFDA5612 BLACK 75
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83789 PLASTIC HFDA5630 BLACK 185
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006046 8 ■

Information Handling Services, 2000

83790 PLASTIC HFDA6522 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83791 PLASTIC HFDE4201 NATURAL EC
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

84209 PLASTIC HID9112
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84210 PLASTIC HID9114
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84211 PLASTIC HID9116
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84212 PLASTIC HID9122
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84213 PLASTIC HID9402
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84214 PLASTIC HID9406
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84215 PLASTIC HID9410
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84216 PLASTIC HID9412/9413
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84217 PLASTIC HID9416
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84218 PLASTIC HID9450
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84219 PLASTIC HID9512/9513
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

69755 PLASTIC HIGH TEMP CERAMIC PUTTY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006047 T

Information Handling Services, 2000

69756 PLASTIC HIGH TEMP MOLD MAKER
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

85057 PLASTIC HIMOD N66GL40
MANF: POLYMER COMPOSITES
....NO TEST DATA AVAILABLE....

85207 PLASTIC HIMOD N66KV20
MANF: POLYMER COMPOSITES
....NO TEST DATA AVAILABLE....

85218 PLASTIC HIMOD N6GL40
MANF: POLYMER COMPOSITES
....NO TEST DATA AVAILABLE....

85221 PLASTIC HIMOD N6KV20
MANF: POLYMER COMPOSITES
....NO TEST DATA AVAILABLE....

85224 PLASTIC HIMOD PCGL40
MANF: POLYMER COMPOSITES
....NO TEST DATA AVAILABLE....

85226 PLASTIC HIMOD PETGL40
MANF: POLYMER COMPOSITES
....NO TEST DATA AVAILABLE....

85229 PLASTIC HIMOD PETGL55
MANF: POLYMER COMPOSITES
....NO TEST DATA AVAILABLE....

85231 PLASTIC HIMOD PPGL50
MANF: POLYMER COMPOSITES
....NO TEST DATA AVAILABLE....

85233 PLASTIC HIMOD PUGL40
MANF: POLYMER COMPOSITES
....NO TEST DATA AVAILABLE....

85235 PLASTIC HIMOD PUKV20
MANF: POLYMER COMPOSITES
....NO TEST DATA AVAILABLE....

84924 PLASTIC HIRI 2 CASTING RESIN (EXTRA)
MANF: PPG INDUSTRIES
....NO TEST DATA AVAILABLE....

84933 PLASTIC HIRI 2 CASTING RESIN (NON-FLAMMABLE)
MANF: PPG INDUSTRIES
....NO TEST DATA AVAILABLE....

67939 PLASTIC HOMOPOLYMER PVC RESIN VC100PM
MANF: BORDEN
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006048 1

Information Handling Services, 2000

67938 PLASTIC HOMOPOLYMER PVC RESIN VC100RE
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67941 PLASTIC HOMOPOLYMER PVC RESIN VC104PM
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67942 PLASTIC HOMOPOLYMER PVC RESIN VC106PM
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67940 PLASTIC HOMOPOLYMER PVC RESIN VC47B
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67935 PLASTIC HOMOPOLYMER PVC RESIN VC54
MANF: ACME CHEMICALS & INSULATION CO
BORDEN
....NO TEST DATA AVAILABLE....

67936 PLASTIC HOMOPOLYMER PVC RESIN VC58
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67937 PLASTIC HOMOPOLYMER PVC RESIN VC95PM
MANF: BORDEN
....NO TEST DATA AVAILABLE....

69593 PLASTIC HOSTAFLON TF
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

80633 PLASTIC HOSTAFLON TF1100
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80634 PLASTIC HOSTAFLON TF1400
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80635 PLASTIC HOSTAFLON TF1620
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80636 PLASTIC HOSTAFLON TF1620F
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80637 PLASTIC HOSTAFLON TF1640
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

69594 PLASTIC HOSTAFLON TF1665
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006049 3

80638 PLASTIC HOSTAFLON TF1740
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80639 PLASTIC HOSTAFLON TF1760
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

69633 PLASTIC HOSTAFLON TF2024
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69597 PLASTIC HOSTAFLON TF2026
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69634 PLASTIC HOSTAFLON TF2051
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69598 PLASTIC HOSTAFLON TF2053
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69635 PLASTIC HOSTAFLON TF2071
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69599 PLASTIC HOSTAFLON TF2103
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69630 PLASTIC HOSTAFLON TF4103
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69631 PLASTIC HOSTAFLON TF4105
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69595 PLASTIC HOSTAFLON TF4215
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69632 PLASTIC HOSTAFLON TF4303
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69596 PLASTIC HOSTAFLON TF4406
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

80640 PLASTIC HOSTAFLON TF5032
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006050 T ■

Information Handling Services, 2000

80641 PLASTIC HOSTAFLON TF5033
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80642 PLASTIC HOSTAFORM C13021
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80643 PLASTIC HOSTAFORM C13031
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80644 PLASTIC HOSTAFORM C2521
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80645 PLASTIC HOSTAFORM C2541
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80646 PLASTIC HOSTAFORM C27021
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80647 PLASTIC HOSTAFORM C32021
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80648 PLASTIC HOSTAFORM C32021AST
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80649 PLASTIC HOSTAFORM C52021
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80650 PLASTIC HOSTAFORM C9021
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80651 PLASTIC HOSTAFORM C9021GV
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80652 PLASTIC HOSTAFORM C9021K
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80653 PLASTIC HOSTAFORM C9021M
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80654 PLASTIC HOSTAFORM C9021TF
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006051 1

Information Handling Services, 2000

80655 PLASTIC HOSTAFORM S27063
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80656 PLASTIC HOSTAFORM S27064
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80657 PLASTIC HOSTAFORM S27073
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80659 PLASTIC HOSTAFORM S27076
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80660 PLASTIC HOSTAFORM S9063
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80661 PLASTIC HOSTAFORM S9064
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80662 PLASTIC HOSTAFORM T1020
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

69638 PLASTIC HOSTALEN
MANF: HOECHST FIBERS

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.14	.02	.00	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

80663 PLASTIC HOSTALEN GA7260
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80664 PLASTIC HOSTALEN GB6450
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80665 PLASTIC HOSTALEN GC7260
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80666 PLASTIC HOSTALEN GD4760
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80667 PLASTIC HOSTALEN GD6250
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80668 PLASTIC HOSTALEN GD7255
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006052 3

Information Handling Services, 2000

80669 PLASTIC HOSTALEN GF4750
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80670 PLASTIC HOSTALEN GF4760
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80671 PLASTIC HOSTALEN GF7740F
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80672 PLASTIC HOSTALEN GF7740F2
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80673 PLASTIC HOSTALEN GF7750M
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80674 PLASTIC HOSTALEN GF9360K
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80675 PLASTIC HOSTALEN GH4765
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80676 PLASTIC HOSTALEN GM5010T2
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80677 PLASTIC HOSTALEN GM5040
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80678 PLASTIC HOSTALEN GM5040T12
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80679 PLASTIC HOSTALEN GM5040T50
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80680 PLASTIC HOSTALEN GM5050
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80681 PLASTIC HOSTALEN GM6255
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80689 PLASTIC HOSTALEN GM7040G
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

80682 PLASTIC HOSTALEN GM7255
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80690 PLASTIC HOSTALEN GM7745
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80683 PLASTIC HOSTALEN GM7746
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80684 PLASTIC HOSTALEN GM8255
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80685 PLASTIC HOSTALEN GM9050F
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80686 PLASTIC HOSTALEN GM9240HT
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80687 PLASTIC HOSTALEN GM9255F
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80688 PLASTIC HOSTALEN GM9350C
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80691 PLASTIC HOSTALEN GR7255P
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

80692 PLASTIC HOSTALEN GUR
MANF: AMERICAN HOECHST
....NO TEST DATA AVAILABLE....

69636 PLASTIC HOSTALEN LD
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69637 PLASTIC HOSTALEN PP
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69640 PLASTIC HOSTALIT
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69641 PLASTIC HOSTALIT Z
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006054 7

Information Handling Services, 2000

69642 PLASTIC HOSTAPOT
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69639 PLASTIC HOSTAPULP
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69643 PLASTIC HOSTYREN
MANF: HOECHST FIBERS
....NO TEST DATA AVAILABLE....

69588 PLASTIC HST11
MANF: HAYSITE DIV., TAYLOR CORP
....NO TEST DATA AVAILABLE....

82066 PLASTIC HUNTSMAN 201
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82067 PLASTIC HUNTSMAN 202
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82068 PLASTIC HUNTSMAN 203
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82069 PLASTIC HUNTSMAN 206
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82070 PLASTIC HUNTSMAN 208
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82071 PLASTIC HUNTSMAN 210
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82072 PLASTIC HUNTSMAN AH703
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82073 PLASTIC HUNTSMAN AH721M
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82074 PLASTIC HUNTSMAN AH731
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82076 PLASTIC HUNTSMAN DP3037
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

82075 PLASTIC HUNTSMAN DP351HF
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82077 PLASTIC HUNTSMAN DP355
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82078 PLASTIC HUNTSMAN HCC201
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82079 PLASTIC HUNTSMAN HCC208
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82080 PLASTIC HUNTSMAN HCC271
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82081 PLASTIC HUNTSMAN HCC360
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82082 PLASTIC HUNTSMAN HCC50
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82083 PLASTIC HUNTSMAN HCC702
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82084 PLASTIC HUNTSMAN HCC705
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82085 PLASTIC HUNTSMAN HCC707
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82086 PLASTIC HUNTSMAN HCC730
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82087 PLASTIC HUNTSMAN HCC760
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82088 PLASTIC HUNTSMAN HCC765
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82089 PLASTIC HUNTSMAN HCC779
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006056 0 ■

Information Handling Services, 2000

82090 PLASTIC HUNTSMAN HCC817
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82091 PLASTIC HUNTSMAN HCC840
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82092 PLASTIC HUNTSMAN HCC850
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82093 PLASTIC HUNTSMAN HCC851
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82097 PLASTIC HUNTSMAN PS312
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82098 PLASTIC HUNTSMAN PS314
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82099 PLASTIC HUNTSMAN PS316
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82100 PLASTIC HUNTSMAN PS318
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82094 PLASTIC HUNTSMAN PS331
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82101 PLASTIC HUNTSMAN PS333
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82102 PLASTIC HUNTSMAN PS335
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82095 PLASTIC HUNTSMAN PS338
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82096 PLASTIC HUNTSMAN PS345
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82103 PLASTIC HUNTSMAN PS350
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006057 2

Information Handling Services, 2000

82104 PLASTIC HUNTSMAN PS351
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82105 PLASTIC HUNTSMAN SEP15
MANF: HUNTSMAN CHEMICAL
....NO TEST DATA AVAILABLE....

82130 PLASTIC INSULSTRUC P1001FR BMC
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82131 PLASTIC INSULSTRUC P5000GP
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82132 PLASTIC INSULSTRUC P5003FR
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

69395 PLASTIC INTERPOL 047-1050
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

82151 PLASTIC IPC104
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82152 PLASTIC IPC120
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82153 PLASTIC IPC170
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82154 PLASTIC IPC171E
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82155 PLASTIC IPC173
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82156 PLASTIC IPC176
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82157 PLASTIC IPC1832
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82158 PLASTIC IPC1833
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F
9999942 0006058 4

Information Handling Services, 2000

82159 PLASTIC IPC1834
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82160 PLASTIC IPC1836
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82161 PLASTIC IPC1837
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82162 PLASTIC IPC5007
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82163 PLASTIC IPC5100
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82164 PLASTIC IPC5303
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82165 PLASTIC IPC5304
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82166 PLASTIC IPC5306
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82167 PLASTIC IPC5308
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

81138 PLASTIC IPC5800
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

81140 PLASTIC IPC6000
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

81142 PLASTIC IPC6025
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

81144 PLASTIC IPC6045
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82141 PLASTIC IPCPX6000
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006059 6 ■

Information Handling Services, 2000

82142 PLASTIC IPCPX6030
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82143 PLASTIC IPCRCF3020
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82144 PLASTIC IPCRCF3030
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82145 PLASTIC IPCRCF3040
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82146 PLASTIC IPCRX171E
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82147 PLASTIC IPCRX173
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82148 PLASTIC IPCRX176
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82149 PLASTIC IPCRX1834
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

82150 PLASTIC IPCRX5308
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

63873 PLASTIC IUPILON POLYCARBONATE GID: EXCAXX
MANF: MITSUBISHI

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.080			06.00	MOD
X	1	024.5	014.5	0.040		00.35	08.00	MOD
X	1	024.5	014.5	0.119			01.70	LARGE
X	1	025.9	014.3	0.080			07.30	MOD
X	1	025.9	014.3	0.040		00.59	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00179.00	

84394 PLASTIC K31
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84395 PLASTIC K43
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006060 2

Information Handling Services, 2000

84396 PLASTIC K61
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84397 PLASTIC K66
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

84393 PLASTIC K77
MANF: COSMIC PLASTICS
....NO TEST DATA AVAILABLE....

68669 PLASTIC KAPTON POLYIMIDE FILM
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68668 PLASTIC KAPTON TYPE H
MANF: DUPONT
....NO TEST DATA AVAILABLE....

81686 PLASTIC KEL-F CTFE CRYSTLLINE
MANF: FLUOROCARBON CORP
....NO TEST DATA AVAILABLE....

85130 PLASTIC KELDAX 6826Q
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85131 PLASTIC KELDAX 8208
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85134 PLASTIC KELDAX 8208Q
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85137 PLASTIC KELDAX 9103
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85140 PLASTIC KELDAX 9105
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85141 PLASTIC KELDAX 9106
MANF: DUPONT
....NO TEST DATA AVAILABLE....

82346 PLASTIC KINEL 3515
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82495 PLASTIC KINEL 4515
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006061 4 ■

Information Handling Services, 2000

82496 PLASTIC KINEL 5504
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82497 PLASTIC KINEL 5505
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82498 PLASTIC KINEL 5508
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82499 PLASTIC KINEL 5511
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82500 PLASTIC KINEL 5514
MANF: RHONE-POULENC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.66	.00	.00		No test data		

82501 PLASTIC KINEL 5517
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82502 PLASTIC KINEL 5518
MANF: RHONE-POULENC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.85	.00	.00		No test data		

84220 PLASTIC KN220
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84221 PLASTIC KN226
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84222 PLASTIC KN230
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

66425 PLASTIC KODAR COPOLYSTER A150 ADHESIVE
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69219 PLASTIC KODAR PETG COPOLYSTER 6763
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

84735 PLASTIC KOSTIL AF1/PA
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006062 6

Information Handling Services, 2000

84736 PLASTIC KOSTIL AF3/PA
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84737 PLASTIC KOSTIL AFL1/PA
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84738 PLASTIC KOSTIL BF/PA
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

62300 PLASTIC KRATON 2701 GID: DKXXXX
MANF: PLASTIC ENGINEERING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.900		00.20	07.10	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.8E-6	27.15	16.21	.01	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00010.87	

69299 PLASTIC KRONITEX 100
MANF: FMC CORP
....NO TEST DATA AVAILABLE....

69297 PLASTIC KRONITEX 1000
MANF: FMC CORP
....NO TEST DATA AVAILABLE....

69296 PLASTIC KRONITEX 50
MANF: FMC CORP
....NO TEST DATA AVAILABLE....

69300 PLASTIC KRONITEX CDD
MANF: FMC CORP
....NO TEST DATA AVAILABLE....

69298 PLASTIC KRONITEX TCP
MANF: FMC CORP
....NO TEST DATA AVAILABLE....

69301 PLASTIC KRONITEX TXP
MANF: FMC CORP
....NO TEST DATA AVAILABLE....

69512 PLASTIC KYNAR
MANF: GULF WANDES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.19	.08	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

84938 PLASTIC KYNAR 461
MANF: PENNWALT CORP
....NO TEST DATA AVAILABLE....

84955 PLASTIC KYNAR 710
MANF: PENNWALT CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006063 8

84958 PLASTIC KYNAR 720
MANF: PENNWALT CORP
....NO TEST DATA AVAILABLE....

84940 PLASTIC KYNAR 721
MANF: PENNWALT CORP
....NO TEST DATA AVAILABLE....

84949 PLASTIC KYNAR 723
MANF: PENNWALT CORP
....NO TEST DATA AVAILABLE....

84960 PLASTIC KYNAR 730
MANF: PENNWALT CORP
....NO TEST DATA AVAILABLE....

84963 PLASTIC KYNAR 736
MANF: PENNWALT CORP
....NO TEST DATA AVAILABLE....

84952 PLASTIC KYNAR 741
MANF: PENNWALT CORP
....NO TEST DATA AVAILABLE....

69513 PLASTIC KYNAR PVDF
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

68910 PLASTIC LA102
MANF: EXXON
....NO TEST DATA AVAILABLE....

68914 PLASTIC LA103
MANF: EXXON
....NO TEST DATA AVAILABLE....

68900 PLASTIC LA104
MANF: EXXON
....NO TEST DATA AVAILABLE....

68901 PLASTIC LA105
MANF: EXXON
....NO TEST DATA AVAILABLE....

68911 PLASTIC LA106
MANF: EXXON
....NO TEST DATA AVAILABLE....

68912 PLASTIC LA113
MANF: EXXON
....NO TEST DATA AVAILABLE....

68902 PLASTIC LA117
MANF: EXXON
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006064 T ■

Information Handling Services, 2000

68915 PLASTIC LA122
MANF: EXXON
....NO TEST DATA AVAILABLE....

68916 PLASTIC LA124
MANF: EXXON
....NO TEST DATA AVAILABLE....

68903 PLASTIC LA129
MANF: EXXON
....NO TEST DATA AVAILABLE....

68913 PLASTIC LA130
MANF: EXXON
....NO TEST DATA AVAILABLE....

68904 PLASTIC LA302
MANF: EXXON
....NO TEST DATA AVAILABLE....

68905 PLASTIC LA305
MANF: EXXON
....NO TEST DATA AVAILABLE....

68906 PLASTIC LA306
MANF: EXXON
....NO TEST DATA AVAILABLE....

68907 PLASTIC LA307
MANF: EXXON
....NO TEST DATA AVAILABLE....

68908 PLASTIC LA308
MANF: EXXON
....NO TEST DATA AVAILABLE....

68909 PLASTIC LA309
MANF: EXXON
....NO TEST DATA AVAILABLE....

68896 PLASTIC LA701
MANF: EXXON
....NO TEST DATA AVAILABLE....

68897 PLASTIC LA702
MANF: EXXON
....NO TEST DATA AVAILABLE....

68898 PLASTIC LA703
MANF: EXXON
....NO TEST DATA AVAILABLE....

68899 PLASTIC LD100
MANF: EXXON
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006065 1

Information Handling Services, 2000

68895 PLASTIC LD700
MANF: EXXON
....NO TEST DATA AVAILABLE....

68537 PLASTIC LE1006/HD3831
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

68535 PLASTIC LE4341/1HD3201
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

68538 PLASTIC LE5301/1HD3824
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

68534 PLASTIC LE5301/HD3201
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

68536 PLASTIC LE6019/HD3469
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

68533 PLASTIC LE6328/HD3201
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

69248 PLASTIC LEXAN 101
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69251 PLASTIC LEXAN 103
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.17	.01	.00		No test data		

69402 PLASTIC LEXAN 104
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69401 PLASTIC LEXAN 121
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69252 PLASTIC LEXAN 123
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69403 PLASTIC LEXAN 124
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69249 PLASTIC LEXAN 141
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.17	.04	.00		No test data		

MSFC-HDBK-527 REV F 9999942 0006066 3

Information Handling Services, 2000

GID: DUCAXX

20370 PLASTIC LEXAN 141 POLYCARBONATE
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81759 PLASTIC LEXAN 141L
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69250 PLASTIC LEXAN 144
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81760 PLASTIC LEXAN 1500
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81761 PLASTIC LEXAN 151
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81762 PLASTIC LEXAN 153
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81763 PLASTIC LEXAN 154
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81764 PLASTIC LEXAN 161
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81765 PLASTIC LEXAN 181
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69398 PLASTIC LEXAN 191
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69404 PLASTIC LEXAN 193
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

80066 PLASTIC LEXAN 2014 POLYCARBONATE
MANF: ENGINEERING PLASTICS
RYAN INSTRUMENTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.800			01.30	LARGE
A	1	025.9	014.3	0.100			00.50	NONE
A	1	030.0	009.0	0.100			02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	319.9	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006067 5

69405 PLASTIC LEXAN 303
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69399 PLASTIC LEXAN 3412 20% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69410 PLASTIC LEXAN 3413 30% GLASS
MANF: AIN PLASTICS
GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	90.6	

TOXICITY

69400 PLASTIC LEXAN 3414 40% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69409 PLASTIC LEXAN 500 10% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

20365 PLASTIC LEXAN 500 POLYCARBONATE GID: DUCAGA

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.10	.01	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

81766 PLASTIC LEXAN 503
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

60927 PLASTIC LEXAN 9030 POLYCARBONATE GID: DUCAXX
MANF: GENERAL ELECTRIC
SPEC: FED L-P-393A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
X	1	025.9	014.3	1.000		00.02	04.80	T	MOD
X	2	025.9	014.3	0.059			00.70		NONE
X	1	025.9	014.3	0.059		00.07	12.00	T	MOD
A	1	030.0	010.0	0.490			00.10		NONE
X	1	050.0	014.7	0.470			03.20		MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.0E-6	.19	.00		

ODOR

RT	RT	WEIGHT	CURE
A	K	00019.95	

TOXICITY

05197 PLASTIC LEXAN 9034 NATURAL POLYCARBONATE GID: DKCACA
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	020.9	014.7	0.023			00.10		NONE
B	1	023.8	014.5	0.031		00.06	09.20		SMALL
X	2	025.9	014.3	0.066			00.10		NONE
X	1	025.9	014.3	0.066		00.07	12.00	T	MOD
X	1	030.0	009.0	0.060		00.07	12.00	T	MOD
I	1	030.0	010.4	0.061		00.06	12.00	T	SMALL
A	1	030.0	010.0	0.450			00.20		NONE
X	2	030.0	010.0	0.061		00.09	12.00	T	LARGE

FSC

RT	FLUID NAME
X	AMMONIA

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	40		70	0.065	0	20
X	MECH	40	72	70	0.065	2	17

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006068 7

05197 PLASTIC LEXAN 9034 NATURAL POLYCARBONATE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.29	

TOXICITY

80298 PLASTIC LEXAN 9034-112 GID: DKXXXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	009.0	0.125		0.01	08.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.19	.01	.00	

ODOR

RT	RT	WEIGHT	CURE
	K	51.30	

TOXICITY

80073 PLASTIC LEXAN 9034-112/A4T COATING OVER DC Q9-6312 GID: DKCAXX

MANF: AMERICAN OPTICAL
GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.114			00.60	MOD
X	1	100.0	020.2	0.115		00.20	06.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-6	.15	.01	.11	

ODOR

RT	RT	WEIGHT	CURE
A	K	33.799	

TOXICITY

69253 PLASTIC LEXAN 920

MANF: GENERAL ELECTRIC

....NO TEST DATA AVAILABLE....

69406 PLASTIC LEXAN 920A

MANF: GENERAL ELECTRIC

....NO TEST DATA AVAILABLE....

62110 PLASTIC LEXAN 940 POLYCARBONATE GID: DUCACA

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	1.020			01.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.16	.00	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

69407 PLASTIC LEXAN 940A

MANF: GENERAL ELECTRIC

....NO TEST DATA AVAILABLE....

20692 PLASTIC LEXAN 9410 WHITE POLYCARBONATE GID: DUCAXX

MANF: GENERAL ELECTRIC

....NO TEST DATA AVAILABLE....

69397 PLASTIC LEXAN 950

MANF: GENERAL ELECTRIC

....NO TEST DATA AVAILABLE....

69408 PLASTIC LEXAN 950A

MANF: GENERAL ELECTRIC

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006069 9

05133 PLASTIC LEXAN 9600 FR NATURAL GID: FJCAXX

MANF: GENERAL ELECTRIC

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	2	023.8	014.5	0.060			00.10	NONE	No test data		No test data						
X	1	023.8	014.5	0.060			01.60	MOD									
A	2	023.8	014.5	0.080			00.10	NONE									
A	1	023.8	014.5	0.080			00.40	NONE									
X	1	030.0	010.0	0.061		00.01	02.60	MOD									

61429 PLASTIC LEXAN 9600 NATURAL POLYCARBONATE GID: DKCACA

MANF: GENERAL ELECTRIC

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.018			01.10	SMALL	No test data		No test data						
A	1	030.0	009.0	0.119			01.50	NONE									
A	1	033.0	014.3	0.018			02.70	SMALL									

80978 PLASTIC LEXAN 9600 NATURAL POLYCARBONATE TOX RATE STUDY

MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	00020.60	

65168 PLASTIC LEXAN 9600-116 POLYCARBONATE GID: DUCAXX

MANF: GENERAL ELECTRIC

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.062		00.11	04.00	LARGE	No test data		No test data						
X	1	030.0	010.0	0.060			04.20	MOD									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	40.2	

61672 PLASTIC LEXAN 9604 FR NATURAL POLYCARBONATE GID: DLCACA

MANF: GENERAL ELECTRIC

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.059			02.70	NONE	No test data		No test data						
X	1	033.0	014.3	1.220			03.90	MOD									
A	1	033.0	014.3	0.059			03.20	SMALL									
X	2	100.0	019.0	1.220		00.17	12.00	T MOD									
X	1	100.0	019.0	1.220		00.12	12.00	T MOD									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	7.2E-7	.11	.00			A	A	00020.65	

06417 PLASTIC LEXAN 9604-71063 POLYCARBONATE GID: DKXXXX

MANF: GENERAL ELECTRIC

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.063			01.40	MOD	No test data		No test data						
X	1	030.0	009.0	0.063			01.20	MOD									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data						A	A	00020.24	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006070 5

81767 PLASTIC LEXAN BE1

MANF: GENERAL ELECTRIC

....NO TEST DATA AVAILABLE....

62268 PLASTIC LEXAN CHROMAFILTER LENS POLYCARBONATE GID: DTCAXX

MANF: PANELGRAPHIC CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.061		00.09	04.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61084 PLASTIC LEXAN F2000 POLYCARBONATE GID: DUCAXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.238			00.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	8.4E-7	.11	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.09	

61573 PLASTIC LEXAN F6000 POLYCARBONATE GID: DKCAXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.053			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06272 PLASTIC LEXAN F60061 POLYCARBONATE GID: DUCAXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.062			02.00	NONE
X	1	033.0	014.3	0.062		00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00019.75	

61692 PLASTIC LEXAN FL900 GID: ETCAXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.235			00.10	NONE
A	1	023.8	014.5	0.235			00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.1E-7	.13	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00021.99	

62111 PLASTIC LEXAN GF3000 POLYCARBONATE GID: DUCAXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.125			01.50	NONE
A	1	033.0	014.3	0.125			01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	2.1E-6	.13	.00		24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.99	

81768 PLASTIC LEXAN HF1110

MANF: GENERAL ELECTRIC

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006071 7

81769 PLASTIC LEXAN HF1130
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81770 PLASTIC LEXAN HF2110
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81771 PLASTIC LEXAN HF2130
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81772 PLASTIC LEXAN HP1
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81773 PLASTIC LEXAN HP2
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81774 PLASTIC LEXAN HP3
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81775 PLASTIC LEXAN HP4
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81776 PLASTIC LEXAN HP5
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

65360 PLASTIC LEXAN MARGARD MR5004-112 GID: DUCAXX
MANF: GENERAL ELECTRIC SPEC: MR 5004-112

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.125			01.75	NONE
A	1	025.9	014.3	0.250			00.50	SMALL
X	1	030.0	009.0	0.125			02.75	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.19	.01	.12	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	18.37	

05760 PLASTIC LEXAN MR4000 SERIES GID: DUCAXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.127			00.10	NONE
A	1	023.8	014.5	0.127			06.00	SMALL
X	2	023.8	014.5	0.123			00.10	NONE
X	1	023.8	014.5	0.123			01.20	NONE
A	1	024.5	014.3	0.125			01.20	SMALL
X	1	025.8	014.3	0.121		00.01	08.40	MOD
X	1	030.0	009.0	0.123			02.80	MOD
X	1	033.2	015.5	0.123			09.30	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	8.9E-6	.18	.00		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.33	

Information Handling Services, 2000

81777 PLASTIC LEXAN OQ1
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

00339 PLASTIC LEXAN POLYCARBONATE CLEAR GID: DUCAXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.0	008.0	0.064			00.10	NONE
A	1	025.0	008.0	0.063			02.60	NONE
A	1	030.0	008.0	0.063			03.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.08	.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

81778 PLASTIC LEXAN PPC4501
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81779 PLASTIC LEXAN PPC4701
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

64072 PLASTIC LEXAN SG403-82311 GID: DTXXXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.120		00.10	02.60	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61766 PLASTIC LEXAN SL29 GID: DKCAXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.134			02.80	SMALL
C	1	023.8	014.5	0.134		00.05	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
X	A 00111.18	

TOXICITY

81780 PLASTIC LEXAN WR2210
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

60751 PLASTIC LEXAN ZELUX M GLASS FILLED GID: DKCAIA
MANF: BLUE BELL PLASTICS
WESTLAKE PLASTICS CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.4E-7	.13	.01		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

81357 PLASTIC LNPD1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81359 PLASTIC LNPDA1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

81368 PLASTIC LNPKL4410
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81369 PLASTIC LNPKL4610
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81370 PLASTIC LNPO1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81371 PLASTIC LNPOFA1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81372 PLASTIC LNPOFA1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81373 PLASTIC LNPP1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81375 PLASTIC LNPPA 6/10
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81376 PLASTIC LNPPA 6/6
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81379 PLASTIC LNPPA1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81381 PLASTIC LNPPA1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81374 PLASTIC LNPPA6
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81389 PLASTIC LNPR1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81392 PLASTIC LNPR5000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81395 PLASTIC LNPRA1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006074 2 ■

81399 PLASTIC LNPRA1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81400 PLASTIC LNPRAL4023
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81402 PLASTIC LNPRCL4536
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81405 PLASTIC LNPRCL4736
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81406 PLASTIC LNPRE5006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81410 PLASTIC LNPREL4536
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81412 PLASTIC LNPREL4736LW
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81417 PLASTIC LNPRL4610
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81431 PLASTIC LNPRL4620
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81554 PLASTIC LNPW1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81556 PLASTIC LNPWA1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

69445 PLASTIC LOMOD B0100
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69451 PLASTIC LOMOD B0150
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69446 PLASTIC LOMOD B0200
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006075 4 ■

69450 PLASTIC LOMOD B0220
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69447 PLASTIC LOMOD B0250
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69448 PLASTIC LOMOD B0800
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69452 PLASTIC LOMOD B0852
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69449 PLASTIC LOMOD R0520
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81559 PLASTIC LUBRICOMP A1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81561 PLASTIC LUBRICOMP AL4030
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81565 PLASTIC LUBRICOMP AL4410
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81567 PLASTIC LUBRICOMP B1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81570 PLASTIC LUBRICOMP BBL4326
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81572 PLASTIC LUBRICOMP BFL4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81575 PLASTIC LUBRICOMP BFL4536
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81577 PLASTIC LUBRICOMP BL4030
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81581 PLASTIC LUBRICOMP BL4410
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006076 6 ■

Information Handling Services, 2000

81582 PLASTIC LUBRICOMP BL4530
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81584 PLASTIC LUBRICOMP C1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81587 PLASTIC LUBRICOMP CL4030
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81588 PLASTIC LUBRICOMP CL4410
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81590 PLASTIC LUBRICOMP D1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81591 PLASTIC LUBRICOMP DC1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81592 PLASTIC LUBRICOMP DF1006
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.14	.01	.00		No test data		

81593 PLASTIC LUBRICOMP DFL4034
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81597 PLASTIC LUBRICOMP DFL4038
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81599 PLASTIC LUBRICOMP DFL4536
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81601 PLASTIC LUBRICOMP DL4010
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81603 PLASTIC LUBRICOMP DL4040
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81604 PLASTIC LUBRICOMP DL4530
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81605 PLASTIC LUBRICOMP F1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006077 8

81969 PLASTIC LUBRICOMP FJL4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81607 PLASTIC LUBRICOMP FL4040
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81609 PLASTIC LUBRICOMP FPC1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81611 PLASTIC LUBRICOMP FPC1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81613 PLASTIC LUBRICOMP FPCF1004M
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81615 PLASTIC LUBRICOMP FPCF1005
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81617 PLASTIC LUBRICOMP FPE1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81620 PLASTIC LUBRICOMP FPEC1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81622 PLASTIC LUBRICOMP FPEC1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81623 PLASTIC LUBRICOMP FPEF1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81625 PLASTIC LUBRICOMP FPEF1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81626 PLASTIC LUBRICOMP FPEF1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81630 PLASTIC LUBRICOMP FPEF1004M
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81632 PLASTIC LUBRICOMP FPEF1005
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006078 T

Information Handling Services, 2000

81634 PLASTIC LUBRICOMP FPEF1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81637 PLASTIC LUBRICOMP FPEFL4035
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81640 PLASTIC LUBRICOMP FPEL4060
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81642 PLASTIC LUBRICOMP FPEL4210
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81643 PLASTIC LUBRICOMP FPEL4320
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81124 PLASTIC LUBRICOMP FPF1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81908 PLASTIC LUBRICOMP FPFC1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81909 PLASTIC LUBRICOMP FPFF1003M
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81910 PLASTIC LUBRICOMP FPFF1004M
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81911 PLASTIC LUBRICOMP FPP1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81912 PLASTIC LUBRICOMP FPPC1003PC
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81914 PLASTIC LUBRICOMP FPPF1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81915 PLASTIC LUBRICOMP FPPF1004M
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81917 PLASTIC LUBRICOMP FPPML3312
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006079 1

Information Handling Services, 2000

81919 PLASTIC LUBRICOMP FPV1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81921 PLASTIC LUBRICOMP FPVC1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81927 PLASTIC LUBRICOMP FPVCL4024
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81929 PLASTIC LUBRICOMP FPVM2550
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81931 PLASTIC LUBRICOMP FPVM3850
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81932 PLASTIC LUBRICOMP FULTON 404D
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81934 PLASTIC LUBRICOMP FULTON 441
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81937 PLASTIC LUBRICOMP FULTON 441D
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81938 PLASTIC LUBRICOMP G1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81940 PLASTIC LUBRICOMP GC1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81942 PLASTIC LUBRICOMP GF1006
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.24	.01	.00		No test data		

81944 PLASTIC LUBRICOMP GFL4022
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81946 PLASTIC LUBRICOMP GFL4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81948 PLASTIC LUBRICOMP GL4030
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006080 8

81950 PLASTIC LUBRICOMP GL4520
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81952 PLASTIC LUBRICOMP GML4334
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81954 PLASTIC LUBRICOMP H1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81955 PLASTIC LUBRICOMP HFL4325
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81956 PLASTIC LUBRICOMP I1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81958 PLASTIC LUBRICOMP IC1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81960 PLASTIC LUBRICOMP IF1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81963 PLASTIC LUBRICOMP IFL4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81964 PLASTIC LUBRICOMP IFL4536
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81966 PLASTIC LUBRICOMP IL4040
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81967 PLASTIC LUBRICOMP IL4410
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81968 PLASTIC LUBRICOMP IL4530
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81970 PLASTIC LUBRICOMP JL4030
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81972 PLASTIC LUBRICOMP K1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006081_T

Information Handling Services, 2000

81973 PLASTIC LUBRICOMP KC1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

81975 PLASTIC LUBRICOMP KF1006
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.28	.02	.00		No test data		

81977 PLASTIC LUBRICOMP KFL4036
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.27	.03	.00		No test data		

82392 PLASTIC LUBRICOMP KFL4536
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.35	.03	.00		No test data		

82394 PLASTIC LUBRICOMP KL4010
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82396 PLASTIC LUBRICOMP KL4020
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82399 PLASTIC LUBRICOMP KL4030
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82398 PLASTIC LUBRICOMP KL4050
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82401 PLASTIC LUBRICOMP KL4320
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82403 PLASTIC LUBRICOMP KL4540
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82404 PLASTIC LUBRICOMP KL4540D
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82407 PLASTIC LUBRICOMP LCL4033
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82410 PLASTIC LUBRICOMP LFL4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F
9999942 0006082 1

Information Handling Services, 2000

82412 PLASTIC LUBRICOMP LL4040
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82414 PLASTIC LUBRICOMP M1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82416 PLASTIC LUBRICOMP MFL4036 HS
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82417 PLASTIC LUBRICOMP ML4040 HS
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82418 PLASTIC LUBRICOMP NYKON P
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82419 PLASTIC LUBRICOMP NYKON Q
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

85364 PLASTIC LUBRICOMP NYKON R
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82421 PLASTIC LUBRICOMP O1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82422 PLASTIC LUBRICOMP OC1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82423 PLASTIC LUBRICOMP OF1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82424 PLASTIC LUBRICOMP OFL4326
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82425 PLASTIC LUBRICOMP OFL4536
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82427 PLASTIC LUBRICOMP OL4040
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82432 PLASTIC LUBRICOMP P1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006083 3

82433 PLASTIC LUBRICOMP PC1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82434 PLASTIC LUBRICOMP PDX4208
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82436 PLASTIC LUBRICOMP PDX5156
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82439 PLASTIC LUBRICOMP PF1006
MANF: L N P CORP

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.50	.01	.00	

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

82441 PLASTIC LUBRICOMP PFL4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82443 PLASTIC LUBRICOMP PFL4536
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82444 PLASTIC LUBRICOMP PL4030
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82445 PLASTIC LUBRICOMP PL4040
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82446 PLASTIC LUBRICOMP PL4310
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82449 PLASTIC LUBRICOMP PL4540
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82451 PLASTIC LUBRICOMP Q1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82454 PLASTIC LUBRICOMP QC1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82456 PLASTIC LUBRICOMP QF1006
MANF: L N P CORP

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.65	.04	.00	

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006084 5 ■

82458 PLASTIC LUBRICOMP QFL4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82460 PLASTIC LUBRICOMP QFL4536
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82461 PLASTIC LUBRICOMP QL4040
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82463 PLASTIC LUBRICOMP QL4410
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82465 PLASTIC LUBRICOMP QL4540
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82467 PLASTIC LUBRICOMP R1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82470 PLASTIC LUBRICOMP RC1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82471 PLASTIC LUBRICOMP RC1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82472 PLASTIC LUBRICOMP RC1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82473 PLASTIC LUBRICOMP RF100-10
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82474 PLASTIC LUBRICOMP RF1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82475 PLASTIC LUBRICOMP RF1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82476 PLASTIC LUBRICOMP RF1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82477 PLASTIC LUBRICOMP RF1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006085 7

Information Handling Services, 2000

82724 PLASTIC LUBRICOMP RFL4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82725 PLASTIC LUBRICOMP RFL4416
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82739 PLASTIC LUBRICOMP RFL4536
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR		TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE	
C	1.0E-6	1.18	.17	.00		No test data			

82746 PLASTIC LUBRICOMP RFL4616
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82747 PLASTIC LUBRICOMP RL4010
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82748 PLASTIC LUBRICOMP RL4040
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82749 PLASTIC LUBRICOMP RL4040 FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82751 PLASTIC LUBRICOMP RL4310
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82752 PLASTIC LUBRICOMP RL4410
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82754 PLASTIC LUBRICOMP RL4540
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR		TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE	
C	1.0E-6	1.40	.07	.00		No test data			

82757 PLASTIC LUBRICOMP RL4610
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82758 PLASTIC LUBRICOMP RL4730
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82761 PLASTIC LUBRICOMP S1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006086 9

82764 PLASTIC LUBRICOMP SFL4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82766 PLASTIC LUBRICOMP SL4040
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82767 PLASTIC LUBRICOMP SL4610
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82768 PLASTIC LUBRICOMP T1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82769 PLASTIC LUBRICOMP TF1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82770 PLASTIC LUBRICOMP TFL4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82771 PLASTIC LUBRICOMP TFL4536
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82772 PLASTIC LUBRICOMP TL4030
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82774 PLASTIC LUBRICOMP TL4410
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82775 PLASTIC LUBRICOMP V1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82777 PLASTIC LUBRICOMP VFL4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82779 PLASTIC LUBRICOMP VICTREX PEEK D450HF30
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82781 PLASTIC LUBRICOMP VICTREX PEEK D450HT15
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82784 PLASTIC LUBRICOMP VICTREX PES 4800G
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006087 0

Information Handling Services, 2000

82787 PLASTIC LUBRICOMP VICTREX PES PDX86174
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82789 PLASTIC LUBRICOMP VL4040
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82791 PLASTIC LUBRICOMP VL4410
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82793 PLASTIC LUBRICOMP VL4530
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82795 PLASTIC LUBRICOMP W1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82797 PLASTIC LUBRICOMP WC1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82798 PLASTIC LUBRICOMP WF1006
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.19	.01	.00		No test data		

82800 PLASTIC LUBRICOMP WFL4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82802 PLASTIC LUBRICOMP WFL4536
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82803 PLASTIC LUBRICOMP WL4030
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82805 PLASTIC LUBRICOMP WL4410
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82809 PLASTIC LUBRICOMP WL4540
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82811 PLASTIC LUBRICOMP X1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82819 PLASTIC LUBRICOMP XC1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006088 2

82824 PLASTIC LUBRICOMP XF1006
MANF: L N P CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.29	.01	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

82827 PLASTIC LUBRICOMP XL4040
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82829 PLASTIC LUBRICOMP Y1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82832 PLASTIC LUBRICOMP YF1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82834 PLASTIC LUBRICOMP YFL4536
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82836 PLASTIC LUBRICOMP YL4030
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82837 PLASTIC LUBRICOMP YL4410
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82840 PLASTIC LUBRICOMP YL4530
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82843 PLASTIC LUBRICOMP Z1000
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82846 PLASTIC LUBRICOMP ZBL4326
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82848 PLASTIC LUBRICOMP ZF1006
MANF: L N P CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.04	.01	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

82849 PLASTIC LUBRICOMP ZFL4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82850 PLASTIC LUBRICOMP ZFL4323
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006089 4 ■

Information Handling Services, 2000

82853 PLASTIC LUBRICOMP ZL4030
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82854 PLASTIC LUBRICOMP ZML4334
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

80531 PLASTIC LUCITE CAST ACRYLIC
MANF: AEROMAT PLASTICS
....NO TEST DATA AVAILABLE....

80840 PLASTIC LUCOBIT 1210
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80841 PLASTIC LURAN 358N
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80842 PLASTIC LURAN 368R
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80843 PLASTIC LURAN 378P
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80844 PLASTIC LURAN 378P7
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80845 PLASTIC LURAN 388S
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80846 PLASTIC LURAN S728K
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80847 PLASTIC LURAN S757R/RK
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80848 PLASTIC LURAN S776S/SK
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80849 PLASTIC LURAN SKR2843
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80850 PLASTIC LURAN SKR2853/1
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006090 0 ■

Information Handling Services, 2000

81426 PLASTIC LUSTRAN ABS1148
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

81427 PLASTIC LUSTRAN ABS248
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

81428 PLASTIC LUSTRAN ABS448
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

81429 PLASTIC LUSTRAN ABS648
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

81430 PLASTIC LUSTRAN ABS743
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84626 PLASTIC LUSTRAN ABS911
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84628 PLASTIC LUSTRAN ABS914HM
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84630 PLASTIC LUSTRAN ABS921UV
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84634 PLASTIC LUSTRAN ABSPG298 PLATED
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84637 PLASTIC LUSTRAN ABSPG298 UNPLATED
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84639 PLASTIC LUSTRAN ELITE LGM
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84641 PLASTIC LUSTRAN ULTRA HX
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84644 PLASTIC LUSTRAN ULTRA MX
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

80851 PLASTIC LUVICAN
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006091 2

Information Handling Services, 2000

81654 PLASTIC M2014
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81655 PLASTIC M2037
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

82133 PLASTIC M4135
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

66222 PLASTIC M53R/H
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

81656 PLASTIC M6204
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

84223 PLASTIC MA3200
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84224 PLASTIC MA5000
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84226 PLASTIC MA6800
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84225 PLASTIC MA9000
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84844 PLASTIC MAGNUM ABS213 RESIN
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84846 PLASTIC MAGNUM ABS341 RESIN
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84848 PLASTIC MAGNUM ABS343 RESIN
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84849 PLASTIC MAGNUM ABS4500UV RESIN
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84850 PLASTIC MAGNUM ABS545 RESIN
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006092 4

Information Handling Services, 2000

84851 PLASTIC MAGNUM ABS9010 RESIN
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84852 PLASTIC MAGNUM ABS9020 RESIN
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84854 PLASTIC MAGNUM ABS9030 RESIN
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84855 PLASTIC MAGNUM ABS9408 RESIN
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84856 PLASTIC MAGNUM ABS941 RESIN
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84858 PLASTIC MAGNUM ABS9450P RESIN
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84860 PLASTIC MAGNUM ABS95CLR RESIN
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84861 PLASTIC MAGNUM ABSFG960 RESIN
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

67497 PLASTIC MARASET 13N
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67363 PLASTIC MARASET 606
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67362 PLASTIC MARASET 607AA
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67361 PLASTIC MARASET 608-10TLS
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67500 PLASTIC MARASET 610
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67504 PLASTIC MARASET 610V
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006093 6

67600 PLASTIC MARASET 612B
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67482 PLASTIC MARASET 6164-2
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67494 PLASTIC MARASET 616N
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67493 PLASTIC MARASET 618
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67491 PLASTIC MARASET 622
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67358 PLASTIC MARASET 641D
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67360 PLASTIC MARASET 670L
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67490 PLASTIC MARASET 676F
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67489 PLASTIC MARASET 677F
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67481 PLASTIC MARASET 7-308
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67357 PLASTIC MARASET F18
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67359 PLASTIC MARASET F180R
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

67476 PLASTIC MARASET M53
MANF: ACME CHEMICALS & INSULATION CO
....NO TEST DATA AVAILABLE....

85021 PLASTIC MARLEX 5502
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006094 8

Information Handling Services, 2000

85022 PLASTIC MARLEX 6003
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85026 PLASTIC MARLEX 6007
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85028 PLASTIC MARLEX BMN 55500
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85049 PLASTIC MARLEX BMN TR880
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85051 PLASTIC MARLEX CL100
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85069 PLASTIC MARLEX CL50
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85067 PLASTIC MARLEX EHM 6001
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85074 PLASTIC MARLEX EHM 6006
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85080 PLASTIC MARLEX EMN TR885
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85088 PLASTIC MARLEX ER9-0002
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85095 PLASTIC MARLEX ER9-0020
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85100 PLASTIC MARLEX HHM 4515
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85103 PLASTIC MARLEX HHM 4903
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85107 PLASTIC MARLEX HHM 5202
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006095 T ■

Information Handling Services, 2000

85110 PLASTIC MARLEX HHM TR210
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85114 PLASTIC MARLEX HHM TR226
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85117 PLASTIC MARLEX HHM TR230
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85119 PLASTIC MARLEX HHM TR232
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85121 PLASTIC MARLEX HHM TR250
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85123 PLASTIC MARLEX HHM TR416
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85126 PLASTIC MARLEX HMN 4550
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85169 PLASTIC MARLEX HMN 50100
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85128 PLASTIC MARLEX HMN 5060
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85133 PLASTIC MARLEX HMN 54140
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85136 PLASTIC MARLEX HMN 5580
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85143 PLASTIC MARLEX HMN 6060
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85146 PLASTIC MARLEX HMN TR938
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85149 PLASTIC MARLEX HMN TR942
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006096 1

Information Handling Services, 2000

85153 PLASTIC MARLEX HMN TR950
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85158 PLASTIC MARLEX HMN TR954
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

84171 PLASTIC MC2100
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84172 PLASTIC MC3100
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84173 PLASTIC MC3500
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84174 PLASTIC MC3600
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84175 PLASTIC MC3700
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84176 PLASTIC MC5161
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84178 PLASTIC MC6561
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84179 PLASTIC MC6800
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

69553 PLASTIC MC901
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

84180 PLASTIC MC9540
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84182 PLASTIC MD9520
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

68584 PLASTIC MELOIN 9000
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006097 3

Information Handling Services, 2000

68581 PLASTIC MELOIN P1 POLYIMIDE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68583 PLASTIC MELOIN P1-15Y POLYIMIDE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68582 PLASTIC MELOIN P1-30X POLYIMIDE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

81583 PLASTIC MERLON 1143
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81585 PLASTIC MERLON 2407
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81586 PLASTIC MERLON 2458
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81589 PLASTIC MERLON 5V-6485
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81594 PLASTIC MERLON 6355
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81595 PLASTIC MERLON 6455
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81596 PLASTIC MERLON 6655
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81598 PLASTIC MERLON 6680
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81600 PLASTIC MERLON 9415
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81602 PLASTIC MERLON AL400 1068 TINT
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81606 PLASTIC MERLON FCR-2405
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006098 5 ■

Information Handling Services, 2000

81608 PLASTIC MERLON FCR-6255
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81610 PLASTIC MERLON HMS 3318
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81612 PLASTIC MERLON M39 (L)
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81614 PLASTIC MERLON M40 (H)
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81616 PLASTIC MERLON M40 (L)
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81619 PLASTIC MERLON M50 (H)
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81618 PLASTIC MERLON M50 (L)
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81621 PLASTIC MERLON RX3 1113 TINT
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81624 PLASTIC MERLON SF-600 0.25 INCHES
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81627 PLASTIC MERLON SF-800 0.25 INCHES
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81628 PLASTIC MERLON SF-810 0.25 INCHES
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81629 PLASTIC MERLON SF-820 0.24 INCHES
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81631 PLASTIC MERLON T-85
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81633 PLASTIC MERLON T-95
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006099 7

Information Handling Services, 2000

82894 PLASTIC METHAFIL J-98/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82898 PLASTIC METHAFIL J-98/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82901 PLASTIC METHAFIL J-98/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82904 PLASTIC METHAFIL J-98/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

84619 PLASTIC MG15F
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84620 PLASTIC MG18
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84621 PLASTIC MG25F
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84622 PLASTIC MG25F-LMP
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84623 PLASTIC MG25F-LMP(F)
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84624 PLASTIC MG25F-LMP-1
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84625 PLASTIC MG35F
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84627 PLASTIC MG35F-01
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84629 PLASTIC MG6-0260
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84631 PLASTIC MG8F-0134
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006100 T ■

Information Handling Services, 2000

NON-METALS BY DESIGNATION

84632 PLASTIC MH19F-0217
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84633 PLASTIC MH19F-0294
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84635 PLASTIC MH2-W254
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84636 PLASTIC MH6-W588
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84638 PLASTIC MH9-02 BLACK
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

69527 PLASTIC MICARTA 20005
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69533 PLASTIC MICARTA 20007
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81887 PLASTIC MICARTA 213
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81888 PLASTIC MICARTA 219
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81889 PLASTIC MICARTA 221
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81890 PLASTIC MICARTA 223
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81891 PLASTIC MICARTA 238
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81892 PLASTIC MICARTA 254
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81893 PLASTIC MICARTA 259-2
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

81894 PLASTIC MICARTA 262
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81895 PLASTIC MICARTA 281
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81896 PLASTIC MICARTA 286
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81897 PLASTIC MICARTA 400
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81898 PLASTIC MICARTA 423
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81899 PLASTIC MICARTA 429
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81900 PLASTIC MICARTA 431
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81901 PLASTIC MICARTA 496
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69523 PLASTIC MICARTA 51
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81902 PLASTIC MICARTA 51F33
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81903 PLASTIC MICARTA 51F60
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81904 PLASTIC MICARTA 51P77
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81905 PLASTIC MICARTA 51P88
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69524 PLASTIC MICARTA 5A2
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006102 3

Information Handling Services, 2000

69525 PLASTIC MICARTA 5A3
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69538 PLASTIC MICARTA 5A4
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69528 PLASTIC MICARTA 76 5A1
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69529 PLASTIC MICARTA 79
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69530 PLASTIC MICARTA 91
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69531 PLASTIC MICARTA 97
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81999 PLASTIC MICARTA H09454
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81906 PLASTIC MICARTA H12426
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81907 PLASTIC MICARTA H17825
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81981 PLASTIC MICARTA H17900
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81982 PLASTIC MICARTA H18331
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81983 PLASTIC MICARTA H18332
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81984 PLASTIC MICARTA H18333
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81985 PLASTIC MICARTA H18720
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006103 5

81986 PLASTIC MICARTA H19128
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81987 PLASTIC MICARTA H19242
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81988 PLASTIC MICARTA H19243
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81989 PLASTIC MICARTA H22033
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81990 PLASTIC MICARTA H23655
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81991 PLASTIC MICARTA H23842
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81992 PLASTIC MICARTA H24721
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81993 PLASTIC MICARTA H24907
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81994 PLASTIC MICARTA H25126
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81995 PLASTIC MICARTA H25219
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81996 PLASTIC MICARTA H26000
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81997 PLASTIC MICARTA H2898
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

81998 PLASTIC MICARTA H5639
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

82000 PLASTIC MICARTA H6-1348
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006104 7 ■

Information Handling Services, 2000

69544 PLASTIC MICARTA HY1216
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69545 PLASTIC MICARTA HY1293
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69548 PLASTIC MICARTA HY1384
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69549 PLASTIC MICARTA HY1457
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69550 PLASTIC MICARTA HY1527
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69534 PLASTIC MICARTA HY1755
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69539 PLASTIC MICARTA HY180
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69540 PLASTIC MICARTA HY180-1
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69546 PLASTIC MICARTA HY1806
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69551 PLASTIC MICARTA HY1828
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69532 PLASTIC MICARTA HY1928
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69537 PLASTIC MICARTA HY2055
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69536 PLASTIC MICARTA HY2140
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69535 PLASTIC MICARTA HY2180
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

69541 PLASTIC MICARTA HY278
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69526 PLASTIC MICARTA HY290-2
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69542 PLASTIC MICARTA HY512
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69543 PLASTIC MICARTA HY689
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69547 PLASTIC MICARTA HY964
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

83891 PLASTIC MICROTHENE
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83877 PLASTIC MICROTHENE MA778
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83878 PLASTIC MICROTHENE MA795
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83879 PLASTIC MICROTHENE MA795-15
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83880 PLASTIC MICROTHENE MC81035
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83881 PLASTIC MICROTHENE MC91381
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83882 PLASTIC MICROTHENE MK91010
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83883 PLASTIC MICROTHENE MK91018
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83888 PLASTIC MICROTHENE MN 722
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006106 0

Information Handling Services, 2000

83884 PLASTIC MICROTHENE MM710-20
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83885 PLASTIC MICROTHENE MM711-20
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83886 PLASTIC MICROTHENE MM718
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83887 PLASTIC MICROTHENE MM720-38
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83889 PLASTIC MICROTHENE MP732-16
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83890 PLASTIC MICROTHENE MP736-16
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83892 PLASTIC MICROTHENE MU760 19% VA
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83893 PLASTIC MICROTHENE MU763 9% VA
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

63499 PLASTIC MINI-TOGGLE ABS GID: DKAIXX
MANF: R E I

		FLAMMABILITY						FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	030.0	010.0			00.30	05.40	NONE	No test data		No test data							

68645 PLASTIC MINLON 10B
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68643 PLASTIC MINLON 11C
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68646 PLASTIC MINLON 12T
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68644 PLASTIC MINLON 20B
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68647 PLASTIC MINLON 21C
MANF: DUPONT
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006107 2

85144 PLASTIC MINLON 22C
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85147 PLASTIC MINLON 91C
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85148 PLASTIC MINLON FR60
MANF: DUPONT
....NO TEST DATA AVAILABLE....

69558 PLASTIC MONOCAST
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

68665 PLASTIC MYLAR
MANF: DUPONT

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.66	.45	.00		No test data		

80539 PLASTIC NEOFLON PFA AP210
MANF: AFTON PLASTICS
....NO TEST DATA AVAILABLE....

80540 PLASTIC NEOFLON PFA AP230
MANF: AFTON PLASTICS
....NO TEST DATA AVAILABLE....

68441 PLASTIC NH20GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68422 PLASTIC NH30GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68442 PLASTIC NH40GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68417 PLASTIC NI20GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68437 PLASTIC NI30GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68418 PLASTIC NI40GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68423 PLASTIC NJ30GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006108 4

Information Handling Services, 2000

68438 PLASTIC NL10GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68419 PLASTIC NL20GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68439 PLASTIC NL30GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68420 PLASTIC NL40GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68440 PLASTIC NL50GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68421 PLASTIC NL60GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68412 PLASTIC NN10GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68415 PLASTIC NN20CF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68432 PLASTIC NN20GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68435 PLASTIC NN30CF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68413 PLASTIC NN30GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68416 PLASTIC NN40CF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68433 PLASTIC NN40GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68414 PLASTIC NN50GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006109 6

Information Handling Services, 2000

68436 PLASTIC NN60CF1000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68434 PLASTIC NN60GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

81299 PLASTIC NOBLEN BC1
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81300 PLASTIC NOBLEN BC2
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81304 PLASTIC NOBLEN BC2A
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81305 PLASTIC NOBLEN BC3
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81307 PLASTIC NOBLEN BC3B
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81309 PLASTIC NOBLEN BC4
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81311 PLASTIC NOBLEN BC4C
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81312 PLASTIC NOBLEN BC5C
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81314 PLASTIC NOBLEN BC6
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81316 PLASTIC NOBLEN BC8
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81318 PLASTIC NOBLEN BC8B
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81319 PLASTIC NOBLEN BC8C
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006110 2

Information Handling Services, 2000

81321 PLASTIC NOBLEN EC8
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81323 PLASTIC NOBLEN EC9
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81324 PLASTIC NOBLEN EC9B
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81326 PLASTIC NOBLEN EX6
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81327 PLASTIC NOBLEN GX20J
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81329 PLASTIC NOBLEN JF40M
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81331 PLASTIC NOBLEN JL20
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81332 PLASTIC NOBLEN MA2
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81334 PLASTIC NOBLEN MA3
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81335 PLASTIC NOBLEN MA3N
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81337 PLASTIC NOBLEN MA4
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81339 PLASTIC NOBLEN MA7
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81342 PLASTIC NOBLEN MA8
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81344 PLASTIC NOBLEN MG3B
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006111 4 ■

Information Handling Services, 2000

81348 PLASTIC NOBLEN MH4
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81350 PLASTIC NOBLEN MH6
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81352 PLASTIC NOBLEN MH8
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81353 PLASTIC NOBLEN MK3G
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81354 PLASTIC NOBLEN MK3H
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81355 PLASTIC NOBLEN MX3A
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81356 PLASTIC NOBLEN X1A
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81358 PLASTIC NOBLEN X1B
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

83849 PLASTIC NORCHEM
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83836 PLASTIC NORCHEM 1028
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83837 PLASTIC NORCHEM 1028A
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83838 PLASTIC NORCHEM 3010
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83839 PLASTIC NORCHEM 3023
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83840 PLASTIC NORCHEM 3025
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006112 6

Information Handling Services, 2000

83841 PLASTIC NORCHEM 3029
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83842 PLASTIC NORCHEM 3414
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83843 PLASTIC NORCHEM 5164
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83844 PLASTIC NORCHEM 5174
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83845 PLASTIC NORCHEM 5304T
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83846 PLASTIC NORCHEM 5305T
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83847 PLASTIC NORCHEM 5307
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83848 PLASTIC NORCHEM 5310T
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83850 PLASTIC NORCHEM 6462HR
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83851 PLASTIC NORCHEM 820
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83852 PLASTIC NORCHEM 831
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83853 PLASTIC NORCHEM 836
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83854 PLASTIC NORCHEM 8404HJ
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83855 PLASTIC NORCHEM 8410ZR
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006113 8

83856 PLASTIC NORCHEM 853
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83857 PLASTIC NORCHEM 860
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83858 PLASTIC NORCHEM NND 5903
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83859 PLASTIC NORCHEM NHD 5905
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83860 PLASTIC NORCHEM NHD 6905
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83861 PLASTIC NORCHEM NHD6908
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83862 PLASTIC NORCHEM NPE 130
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83863 PLASTIC NORCHEM NPE 190
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83864 PLASTIC NORCHEM NPE 191
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83865 PLASTIC NORCHEM NPE 195
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83866 PLASTIC NORCHEM NPE 210
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83867 PLASTIC NORCHEM NPE 253
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83868 PLASTIC NORCHEM NPE 265
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83869 PLASTIC NORCHEM NPE 283
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006114 T

Information Handling Services, 2000

83870 PLASTIC NORCHEM NPE 293
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83871 PLASTIC NORCHEM NPE 3801
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83872 PLASTIC NORCHEM NPE 3855
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83873 PLASTIC NORCHEM NPE 3865
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83874 PLASTIC NORCHEM NPE 510
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83875 PLASTIC NORCHEM NPE 510-3
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83876 PLASTIC NORCHEM NPP 1602WF
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

69728 PLASTIC NORYL
MANF: NYTEF PLASTICS, LTD.
....NO TEST DATA AVAILABLE....

81781 PLASTIC NORYL 1222
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81782 PLASTIC NORYL 1390
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81783 PLASTIC NORYL 1391
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81784 PLASTIC NORYL 722
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69425 PLASTIC NORYL 731
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.25	.00	.00		No test data		

81785 PLASTIC NORYL 844
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006115 1

Information Handling Services, 2000

81786 PLASTIC NORYL 888
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69444 PLASTIC NORYL CRT200
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81787 PLASTIC NORYL EN185
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81788 PLASTIC NORYL EN212
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69437 PLASTIC NORYL GFN2
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.08	.00	.00		No test data		

69427 PLASTIC NORYL GFN3
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.04	.03	.00		No test data		

81789 PLASTIC NORYL GTX 810
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81790 PLASTIC NORYL GTX 820
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81791 PLASTIC NORYL GTX 830
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81792 PLASTIC NORYL GTX 910
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69443 PLASTIC NORYL HB235
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69424 PLASTIC NORYL HS1000
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69436 PLASTIC NORYL HS2000
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006116 3 ■

69434 PLASTIC NORYL N190
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69435 PLASTIC NORYL N225
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69426 PLASTIC NORYL N300
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.25	.00	.00	

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

69432 PLASTIC NORYL PC180
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81793 PLASTIC NORYL PLUS CRN410
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81794 PLASTIC NORYL PLUS CRN639
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81795 PLASTIC NORYL PLUS RNF420
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81796 PLASTIC NORYL PLUS RNF430
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81797 PLASTIC NORYL PLUS SPN410
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81798 PLASTIC NORYL PLUS SPN420
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81799 PLASTIC NORYL PLUS SPN422L
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81800 PLASTIC NORYL PLUS SPN580
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81801 PLASTIC NORYL PLUS SPN585H
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81802 PLASTIC NORYL PLUS UVN580
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006117 5

69439 PLASTIC NORYL PN235
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69428 PLASTIC NORYL PX0722
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69429 PLASTIC NORYL PX1222
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69430 PLASTIC NORYL PX1265
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69442 PLASTIC NORYL PX1390
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69431 PLASTIC NORYL PX1391
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69440 PLASTIC NORYL PX844
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69441 PLASTIC NORYL PX888
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69423 PLASTIC NORYL SE 100
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69438 PLASTIC NORYL SE1-CFN2
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81803 PLASTIC NORYL SE1/GFN2
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81804 PLASTIC NORYL SE1/GFN3
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69433 PLASTIC NORYL UV180
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81265 PLASTIC NOVATEC-L F101A
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006118 7 ■

Information Handling Services, 2000

81267 PLASTIC NOVATEC-L F121
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81268 PLASTIC NOVATEC-L F131
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81275 PLASTIC NOVATEC-L F141
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81276 PLASTIC NOVATEC-L F155
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81277 PLASTIC NOVATEC-L F161
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81279 PLASTIC NOVATEC-L F250
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81281 PLASTIC NOVATEC-L F261
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81264 PLASTIC NOVATEC-L FL00
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81282 PLASTIC NOVATEC-L L300
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81285 PLASTIC NOVATEC-L L320
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81288 PLASTIC NOVATEC-L L330
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81290 PLASTIC NOVATEC-L M400
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81291 PLASTIC NOVATEC-L M420
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81293 PLASTIC NOVATEC-L M430
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006119 9

Information Handling Services, 2000

81295 PLASTIC NOVATEC-L M450
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81297 PLASTIC NOVATEC-L M460
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

80852 PLASTIC NOVOLEN 1120HX
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80853 PLASTIC NOVOLEN 1120LX
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80854 PLASTIC NOVOLEN 1120NX
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80855 PLASTIC NOVOLEN 1300E
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80856 PLASTIC NOVOLEN 1300Z
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80857 PLASTIC NOVOLEN 1320H
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80858 PLASTIC NOVOLEN 1320L
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80859 PLASTIC NOVOLEN 3300HX
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

85151 PLASTIC NUCREL 010
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85152 PLASTIC NUCREL 035
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85154 PLASTIC NUCREL 403
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85156 PLASTIC NUCREL 410
MANF: DUPONT
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006120 5 ■

DATE: 12/23/88
NON-METALS BY DESIGNATION

85157 PLASTIC NUCREL 535
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85159 PLASTIC NUCREL 599
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85161 PLASTIC NUCREL 699
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85162 PLASTIC NUCREL 714
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85164 PLASTIC NUCREL 925
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85166 PLASTIC NUCREL 960
MANF: DUPONT
....NO TEST DATA AVAILABLE....

69366 PLASTIC NUPOL 46-4001
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69368 PLASTIC NUPOL 46-4003
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69367 PLASTIC NUPOL 46-4004
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69369 PLASTIC NUPOL 46-4008
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69370 PLASTIC NUPOL 46-4013
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69376 PLASTIC NUPOL 46-4020
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69371 PLASTIC NUPOL 46-4076
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69377 PLASTIC NUPOL 46-4250
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006121 7

Information Handling Services, 2000

69372 PLASTIC NUPOL 46-4400
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69378 PLASTIC NUPOL 46-4421
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69373 PLASTIC NUPOL 46-4435
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69379 PLASTIC NUPOL 46-4440
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69374 PLASTIC NUPOL 46-8000
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69375 PLASTIC NUPOL 46-8016
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

68428 PLASTIC NY-10GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68409 PLASTIC NY-20GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68431 PLASTIC NY-30CF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68429 PLASTIC NY-30GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68410 PLASTIC NY-40GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68430 PLASTIC NY-50GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68411 PLASTIC NY-60GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

82858 PLASTIC NY-KON I
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006122 9

Information Handling Services, 2000

82860 PLASTIC NY-KON P
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82862 PLASTIC NY-KON Q
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82865 PLASTIC NY-KON R
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82907 PLASTIC NYAFIL 6
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82910 PLASTIC NYAFIL 6/12
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82914 PLASTIC NYAFIL G-1/10/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82915 PLASTIC NYAFIL G-1/30 AND G-1/30/HS
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82919 PLASTIC NYAFIL G-1/30/MS/5
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82921 PLASTIC NYAFIL G-1/30/SI/2
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82923 PLASTIC NYAFIL G-1/30/TF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82925 PLASTIC NYAFIL G-1/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82928 PLASTIC NYAFIL G-1/40/MS/5
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82930 PLASTIC NYAFIL G-1/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82932 PLASTIC NYAFIL G-3/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006123 0 ■

Information Handling Services, 2000

82934 PLASTIC NYAFIL G-3/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82937 PLASTIC NYAFIL G-4/35
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82939 PLASTIC NYAFIL G-4/45
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82941 PLASTIC NYAFIL G-8/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82944 PLASTIC NYAFIL J-1/15/MF/25
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82947 PLASTIC NYAFIL J-1/20/FR
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82951 PLASTIC NYAFIL J-1/30 AND J-1/30/HS
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82953 PLASTIC NYAFIL J-1/30/MS/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82957 PLASTIC NYAFIL J-1/30/MS/5
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82959 PLASTIC NYAFIL J-1/30/SI/3
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82961 PLASTIC NYAFIL J-1/30/TF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82964 PLASTIC NYAFIL J-1/33 AND J-1/33/HS
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82968 PLASTIC NYAFIL J-1/33/TF/13/SI/2
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82971 PLASTIC NYAFIL J-1/40/MU/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006124 2

Information Handling Services, 2000

82973 PLASTIC NYAFIL J-1/43
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82975 PLASTIC NYAFIL J-1/CF/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82978 PLASTIC NYAFIL J-1/CF/30/TF/13/SI/2
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82980 PLASTIC NYAFIL J-1/CP/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82984 PLASTIC NYAFIL J-17/20/VO
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82986 PLASTIC NYAFIL J-17/20/VO/TF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82991 PLASTIC NYAFIL J-17/30/VO
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82994 PLASTIC NYAFIL J-2/30/VO
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82995 PLASTIC NYAFIL J-29/33
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82996 PLASTIC NYAFIL J-29/8/MB/22
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82998 PLASTIC NYAFIL J-3/15/MF/25
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83000 PLASTIC NYAFIL J-3/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83005 PLASTIC NYAFIL J-3/30/VO
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83008 PLASTIC NYAFIL J-3/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006125 4

Information Handling Services, 2000

83016 PLASTIC NYAFIL J-4/30/TF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83017 PLASTIC NYAFIL J-4/30/VO
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83020 PLASTIC NYAFIL J-4/35
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83022 PLASTIC NYAFIL J-4/45
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83023 PLASTIC NYAFIL J-4/CF/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83025 PLASTIC NYAFIL J-6/25
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83027 PLASTIC NYAFIL J-6/50
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83031 PLASTIC NYAFIL J-7/13
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83032 PLASTIC NYAFIL J-7/33
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83035 PLASTIC NYAFIL J-7/43
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83038 PLASTIC NYAFIL J-70/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83047 PLASTIC NYAFIL J-71/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83050 PLASTIC NYAFIL J-8/13
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83053 PLASTIC NYAFIL J-8/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006126 6 ■

Information Handling Services, 2000

83055 PLASTIC NYAFIL J-8/33
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83057 PLASTIC NYAFIL J-8/43
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83058 PLASTIC NYAFIL MG-1/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83060 PLASTIC NYAFIL NY-1/EC
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83064 PLASTIC NYAFIL NY-1/MS/5
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83065 PLASTIC NYAFIL NY-1/SI/5
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83072 PLASTIC NYAFIL NY-1/TC/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83074 PLASTIC NYAFIL NY-1/TF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83076 PLASTIC NYAFIL NY-16/MF/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83079 PLASTIC NYAFIL NY-17/MF/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83238 PLASTIC NYAFIL NY-3/EC
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83239 PLASTIC NYAFIL NY-3/TC/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83240 PLASTIC NYAFIL NY-7
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83241 PLASTIC NYAFIL NY-8
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006127 8

Information Handling Services, 2000

83242 PLASTIC NYAFIL NY-8/MF/36
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83081 PLASTIC NYAFIL NY3/20/75
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83243 PLASTIC NYAFIL TYPE 6/10 NYLON UNREINFORCED
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83244 PLASTIC NYAFIL UNREINFORCED 612
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83245 PLASTIC NYAFIL UNREINFORCED SUPER TOUGH TYPE 12
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83246 PLASTIC NYAFIL UNREINFORCED TYPE 12
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83247 PLASTIC NYAFIL UNREINFORCED TYPE 6
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83248 PLASTIC NYAFIL UNREINFORCED TYPE 66
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83251 PLASTIC NYAFIL VO NY-7/VO
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83249 PLASTIC NYAFIL XYLON FR
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83250 PLASTIC NYAFIL XYLON/VO
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

81635 PLASTIC NYDUR BC 303
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81636 PLASTIC NYDUR BC 402
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81638 PLASTIC NYDUR BKV 130
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006128 T

Information Handling Services, 2000

81639 PLASTIC HYDUR BKV 140
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

82411 PLASTIC HYLAFIL G-3/30 MS/5
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82413 PLASTIC HYLAFIL G-3/40 MS/5
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82415 PLASTIC HYLAFIL J-1/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82426 PLASTIC HYLAFIL J-3/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

82428 PLASTIC HYLAFIL POLYCARBAFIL G-50/20
MANF: WILSON FIBERFIL

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.12	.00	.00		No test data		

69566 PLASTIC HYLAFLOW
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

69554 PLASTIC HYLATRON GSM
MANF: GULF WANDES

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	3.41	.01	.00		No test data		

80532 PLASTIC HYLATRON HSB NYLON
MANF: AEROMAT PLASTICS
....NO TEST DATA AVAILABLE....

80533 PLASTIC HYLATRON HSN NYLON
MANF: AEROMAT PLASTICS
....NO TEST DATA AVAILABLE....

84522 PLASTIC NYLON 1000
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84521 PLASTIC NYLON 1000-1
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84519 PLASTIC NYLON 1000-2
MANF: CELANESE
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006129 1

Information Handling Services, 2000

84518 PLASTIC NYLON 1000-4
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84516 PLASTIC NYLON 1000-6
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84513 PLASTIC NYLON 1003
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84511 PLASTIC NYLON 1003-1
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84509 PLASTIC NYLON 1003-2
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84227 PLASTIC NYLON 1003-4
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84476 PLASTIC NYLON 1003-6
MANF: CELANESE
....NO TEST DATA AVAILABLE....

69552 PLASTIC NYLON 101
MANF: GULF WANDES

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	3.03	.01	.00		No test data		

84477 PLASTIC NYLON 1100
MANF: CELANESE
....NO TEST DATA AVAILABLE....

80820 PLASTIC NYLON 12 MOLDING GRADE AZM030
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

84478 PLASTIC NYLON 1200
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84479 PLASTIC NYLON 1300
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84480 PLASTIC NYLON 1310
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84481 PLASTIC NYLON 1310-1
MANF: CELANESE
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006130 8 ■

84483 PLASTIC NYLON 1310-2
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84482 PLASTIC NYLON 1310-4
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84484 PLASTIC NYLON 1310-6
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84485 PLASTIC NYLON 1400
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84486 PLASTIC NYLON 1400-1
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84523 PLASTIC NYLON 1400-2
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84487 PLASTIC NYLON 1403-1
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84488 PLASTIC NYLON 1403-2
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84489 PLASTIC NYLON 1500
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84490 PLASTIC NYLON 1500-1
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84492 PLASTIC NYLON 1500-2
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84493 PLASTIC NYLON 1503-1
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84495 PLASTIC NYLON 1503-2
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84497 PLASTIC NYLON 1600
MANF: CELANESE
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006131 T

Information Handling Services, 2000

84498 PLASTIC NYLON 1600-1
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84500 PLASTIC NYLON 1600-2
MANF: CELANESE
....NO TEST DATA AVAILABLE....

68528 PLASTIC NYLON 401
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

68529 PLASTIC NYLON 402
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

68513 PLASTIC NYLON 404
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

84405 PLASTIC NYLON 406
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

68514 PLASTIC NYLON 409
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

68515 PLASTIC NYLON 451
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

68516 PLASTIC NYLON 452
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

68517 PLASTIC NYLON 453
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

68518 PLASTIC NYLON 454
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

68541 PLASTIC NYLON 6
MANF: DIXON INDUSTRIES

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.50	.01	.00		No test data		

68546 PLASTIC NYLON 6.6 30% CF 15% TFE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68544 PLASTIC NYLON 6.6 33% GLASS
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006132 1

DATE: 12/23/88
NON-METALS BY DESIGNATION

69722 PLASTIC NYLON 6/12
MANF: NYTEF PLASTICS, LTD.
....NO TEST DATA AVAILABLE....

68543 PLASTIC NYLON 6/6 10% GLASS
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68545 PLASTIC NYLON 6/6 MINERAL FILLED
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68520 PLASTIC NYLON 600
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

68519 PLASTIC NYLON 601
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

68522 PLASTIC NYLON 603
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

68521 PLASTIC NYLON 607
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

68523 PLASTIC NYLON 609
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

68524 PLASTIC NYLON 615
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

84501 PLASTIC NYLON 7010
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84502 PLASTIC NYLON 7013
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84503 PLASTIC NYLON 7020
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84504 PLASTIC NYLON 7023
MANF: CELANESE
....NO TEST DATA AVAILABLE....

84505 PLASTIC NYLON 7030
MANF: CELANESE
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

84506 PLASTIC NYLON 7033
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85303 PLASTIC NYLON 7420
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85304 PLASTIC NYLON 7423
MANF: CELANESE
....NO TEST DATA AVAILABLE....

69721 PLASTIC NYLON MP/FILLED
MANF: NYTEF PLASTICS, LTD.
....NO TEST DATA AVAILABLE....

85305 PLASTIC NYLON N186
MANF: CELANESE
....NO TEST DATA AVAILABLE....

85306 PLASTIC NYLON N224
MANF: CELANESE
....NO TEST DATA AVAILABLE....

69723 PLASTIC NYLON NAST TYPE 6
MANF: NYTEF PLASTICS, LTD.
....NO TEST DATA AVAILABLE....

68525 PLASTIC NYLON NX 2011
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

68527 PLASTIC NYLON NX 5703
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

68526 PLASTIC NYLON NX 6200
MANF: CUSTOM RESINS
....NO TEST DATA AVAILABLE....

67765 PLASTIC NYPEL 2314
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67766 PLASTIC NYPEL 2314 FCAT
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67767 PLASTIC NYPEL 2360
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67770 PLASTIC NYPEL 2365G
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006134 5

Information Handling Services, 2000

67763 PLASTIC NYPEL 6033G
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

68498 PLASTIC NYSYN 28-7XL
MANF: COPOLYMER RUBBER AND CHEM CORP
....NO TEST DATA AVAILABLE....

69790 PLASTIC OILON PV80 POLYACETAL FILLED HOMO
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

68006 PLASTIC OPACIFIER 341
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

80780 PLASTIC ORGAMIDE RMNO P40 CD
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80781 PLASTIC ORGAMIDE RMNOCD
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80782 PLASTIC ORGAMIDE RZM 30
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80783 PLASTIC ORGAMIDE RZM15
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80784 PLASTIC ORGATER TMNO
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80785 PLASTIC ORGATER TZM 20
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80786 PLASTIC ORGATER TZM 30 W8
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

81547 PLASTIC OS 2824
MANF: MOBIL OIL CORP
....NO TEST DATA AVAILABLE....

68825 PLASTIC P1185A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

80860 PLASTIC PALATAL P6 30/35% GLASS
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006135 7

Information Handling Services, 2000

80861 PLASTIC PALATAL P6 40/45% GLASS
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80862 PLASTIC PALATAL P6 50/55% GLASS (IB)
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80863 PLASTIC PALATAL P6 55/60% GLASS
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80864 PLASTIC PALATAL P6 60/70% GLASS
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80865 PLASTIC PALATAL P6 70/75% GLASS
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80866 PLASTIC PALATAL P6 UNREINFORCED
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

68008 PLASTIC PARIFIF EMULSION 135-40
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67954 PLASTIC PASTE PVC RESINS 410M
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67953 PLASTIC PASTE PVC RESINS VC-405
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67955 PLASTIC PASTE PVC RESINS VC-411
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67956 PLASTIC PASTE PVC RESINS VC-436/VC-437
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67957 PLASTIC PASTE PVC RESINS VC-440
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67958 PLASTIC PASTE PVC RESINS VC1069
MANF: BORDEN
....NO TEST DATA AVAILABLE....

67738 PLASTIC PAXON 3201
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006136 9 ■

Information Handling Services, 2000

DATE: 12/23/88
NON-METALS BY DESIGNATION

67723 PLASTIC PAXON 3204
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67737 PLASTIC PAXON 3205
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67722 PLASTIC PAXON 3207
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67736 PLASTIC PAXON 3303
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67735 PLASTIC PAXON 4700
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67717 PLASTIC PAXON AA-50-003
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67716 PLASTIC PAXON AA-50-60
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67714 PLASTIC PAXON AA50-180
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67715 PLASTIC PAXON AA50-250
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67713 PLASTIC PAXON AA55-100
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67726 PLASTIC PAXON AA55-400
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67740 PLASTIC PAXON AA55-60
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

80613 PLASTIC PAXON AA55-600
MANF: ALLIED FIBERS
....NO TEST DATA AVAILABLE....

67712 PLASTIC PAXON AA55-80
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006137 0

Information Handling Services, 2000

67739 PLASTIC PAXON AA60-003
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67724 PLASTIC PAXON AA60-007
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67732 PLASTIC PAXON AB40-003
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67731 PLASTIC PAXON AB50-003
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67730 PLASTIC PAXON AB55-003
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67729 PLASTIC PAXON AC40-003
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67728 PLASTIC PAXON AC55-003
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67721 PLASTIC PAXON AE50-003
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67727 PLASTIC PAXON AF40-003
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67720 PLASTIC PAXON AG55-003
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67719 PLASTIC PAXON AK53-004
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67725 PLASTIC PAXON AP60-007
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67733 PLASTIC PAXON BA50-100
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

80614 PLASTIC PAXON FD60-018
MANF: ALLIED FIBERS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006138 2 ■

Information Handling Services, 2000

67734 PLASTIC PAXON FP60-018
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

68560 PLASTIC PBT (RYNITE)
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68471 PLASTIC PC-000/10T
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68446 PLASTIC PC-000/15T
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68472 PLASTIC PC-000/20T
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68445 PLASTIC PC-000/5T
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68451 PLASTIC PC-10CF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68475 PLASTIC PC-10GF/000 FR
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68449 PLASTIC PC-20CF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68476 PLASTIC PC-20CF/15T
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68443 PLASTIC PC-20GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68447 PLASTIC PC-20GF/15T
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68474 PLASTIC PC-30CF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68452 PLASTIC PC-30CF/20
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006139 4

Information Handling Services, 2000

68424 PLASTIC PC-30GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68473 PLASTIC PC-30GF/15T
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68450 PLASTIC PC-40CF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68444 PLASTIC PC-40GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68448 PLASTIC PC-40GF/15T
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

82870 PLASTIC PDX-82427
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82874 PLASTIC PDX-82428
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82877 PLASTIC PDX-83238
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82878 PLASTIC PDX-83392
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82881 PLASTIC PDX-83393
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82884 PLASTIC PDX-84356
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82886 PLASTIC PDX-84357
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82889 PLASTIC PDX-84367 PEI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82866 PLASTIC PDX-84369 PBT
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006140 0

Information Handling Services, 2000

82891 PLASTIC PDX-84440 EVA
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

69503 PLASTIC PE 100
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

84183 PLASTIC PE 1007
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84184 PLASTIC PE 1008.5
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

68858 PLASTIC PE 102
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68845 PLASTIC PE 103
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68856 PLASTIC PE 107
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68846 PLASTIC PE 108
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68841 PLASTIC PE 109
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

84186 PLASTIC PE 117A
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

68865 PLASTIC PE 118
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68852 PLASTIC PE 119
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

84187 PLASTIC PE 1205
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84188 PLASTIC PE 1207
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006141 2

Information Handling Services, 2000

68842 PLASTIC PE 121
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68816 PLASTIC PE 122
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

84189 PLASTIC PE 1220
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

68843 PLASTIC PE 125
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68866 PLASTIC PE 126
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

84190 PLASTIC PE 1260
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

68853 PLASTIC PE 127
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68867 PLASTIC PE 128
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

84191 PLASTIC PE 1400
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84192 PLASTIC PE 1408.5
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84193 PLASTIC PE 1409
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84194 PLASTIC PE 1412
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

68870 PLASTIC PE 142
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68854 PLASTIC PE 143
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006142 4 ■

Information Handling Services, 2000

68860 PLASTIC PE 171
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68847 PLASTIC PE 172
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68868 PLASTIC PE 178
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68855 PLASTIC PE 179
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68861 PLASTIC PE 181
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68848 PLASTIC PE 200
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

69505 PLASTIC PE 2000
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

68862 PLASTIC PE 202
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68849 PLASTIC PE 204
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68850 PLASTIC PE 204C5239
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68863 PLASTIC PE 204C595
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68869 PLASTIC PE 207
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

69500 PLASTIC PE 207F
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

68864 PLASTIC PE 211
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006143 6

Information Handling Services, 2000

68851 PLASTIC PE 216
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68857 PLASTIC PE 220
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

69506 PLASTIC PE 222
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

68844 PLASTIC PE 256
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

69501 PLASTIC PE 307TS
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

84195 PLASTIC PE 4538A
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84196 PLASTIC PE 4538B
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

84197 PLASTIC PE 5104
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

68814 PLASTIC PE101
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68859 PLASTIC PE106
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68815 PLASTIC PE111
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

84185 PLASTIC PE1117A
MANF: CHEVRON CHEMICAL
....NO TEST DATA AVAILABLE....

83948 PLASTIC PE25
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83949 PLASTIC PE2FR
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006144 8

Information Handling Services, 2000

83950 PLASTIC PE3CC3
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83951 PLASTIC PE47MF1
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

80787 PLASTIC PEBAX 2533
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80788 PLASTIC PEBAX 3533
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80789 PLASTIC PEBAX 4011
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80790 PLASTIC PEBAX 4033
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80791 PLASTIC PEBAX 5512
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80792 PLASTIC PEBAX 5533
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80793 PLASTIC PEBAX 5562
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80794 PLASTIC PEBAX 6312
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80795 PLASTIC PEBAX 6333
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80796 PLASTIC PEBAX SERIES 62
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

68576 PLASTIC PEEK
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68004 PLASTIC PEN CLEAR
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006145 T ■

Information Handling Services, 2000

68005 PLASTIC PEN-1031
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

68539 PLASTIC PENNLON UHMWPE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

05782 PLASTIC PENTON GID: DKXXXX
MANF: ROCKELL
....NO TEST DATA AVAILABLE....

61717 PLASTIC PES-200P GID: DUCIXX
MANF: JCI AMERICA

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.060			00.20	NONE	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	1.0E-6	1.04	.00	.00		A	V	00019.04	

81641 PLASTIC PETLON 3530
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81644 PLASTIC PETLON 4530
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81645 PLASTIC PETLON 7530
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

83903 PLASTIC PETOTHENE KR92562
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

67771 PLASTIC PETRA 130 FR
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67773 PLASTIC PETRA 140
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67774 PLASTIC PETRA 149
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67775 PLASTIC PETRA 150
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

67776 PLASTIC PETRA 230
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006146 1
Information Handling Services, 2000

83894 PLASTIC PETROTHENE FM704
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83895 PLASTIC PETROTHENE FR412
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83896 PLASTIC PETROTHENE FR424
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83897 PLASTIC PETROTHENE FX702
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83898 PLASTIC PETROTHENE FX703
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83899 PLASTIC PETROTHENE FX705
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83900 PLASTIC PETROTHENE KR21017
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83901 PLASTIC PETROTHENE KR901028
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83902 PLASTIC PETROTHENE KR92561
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

84739 PLASTIC PETROTHENE LB 603
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84740 PLASTIC PETROTHENE LB 851
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84742 PLASTIC PETROTHENE LB 861
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

83904 PLASTIC PETROTHENE LB710
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83905 PLASTIC PETROTHENE LB742
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006147 3

83906 PLASTIC PETROTHENE LB830
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83907 PLASTIC PETROTHENE LB832
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83908 PLASTIC PETROTHENE LC732
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83911 PLASTIC PETROTHENE LR580
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83912 PLASTIC PETROTHENE LR586
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83909 PLASTIC PETROTHENE LR734
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83910 PLASTIC PETROTHENE LR920
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

84744 PLASTIC PETROTHENE LS 404
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84746 PLASTIC PETROTHENE LS 506
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84747 PLASTIC PETROTHENE LS 509
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84749 PLASTIC PETROTHENE LS 511
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84773 PLASTIC PETROTHENE LS 514
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84775 PLASTIC PETROTHENE LS 523
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84777 PLASTIC PETROTHENE LS 525
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006148 5

Information Handling Services, 2000

84779 PLASTIC PETROTHENE LS 528
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84781 PLASTIC PETROTHENE LS 530
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84785 PLASTIC PETROTHENE LS 545
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84786 PLASTIC PETROTHENE LS 556
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84788 PLASTIC PETROTHENE LS 606
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84790 PLASTIC PETROTHENE LS 609
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84793 PLASTIC PETROTHENE LS 618
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84795 PLASTIC PETROTHENE LS 630
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84798 PLASTIC PETROTHENE LS 901
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84800 PLASTIC PETROTHENE LY 656
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84802 PLASTIC PETROTHENE NA 117
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84804 PLASTIC PETROTHENE NA 202
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84806 PLASTIC PETROTHENE NA 208
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84808 PLASTIC PETROTHENE NA 213
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006149 7

Information Handling Services, 2000

84815 PLASTIC PETROTHENE NA 225
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84817 PLASTIC PETROTHENE NA 226
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84820 PLASTIC PETROTHENE NA 241
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84821 PLASTIC PETROTHENE NA 246
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84823 PLASTIC PETROTHENE NA 249
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84825 PLASTIC PETROTHENE NA 254
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84828 PLASTIC PETROTHENE NA 270
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84831 PLASTIC PETROTHENE NA 295
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

83913 PLASTIC PETROTHENE NA171
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83914 PLASTIC PETROTHENE NA301
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83915 PLASTIC PETROTHENE NA301-06
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83916 PLASTIC PETROTHENE NA307
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83917 PLASTIC PETROTHENE NA309
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83918 PLASTIC PETROTHENE NA310-05
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006150 3

Information Handling Services, 2000

DATE: 12/23/88
NON-METALS BY DESIGNATION

83919 PLASTIC PETROTHENE NA310-06
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83920 PLASTIC PETROTHENE XL3512
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83921 PLASTIC PETROTHENE XL3700
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83922 PLASTIC PETROTHENE XL5421
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83923 PLASTIC PETROTHENE XL5422
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83924 PLASTIC PETROTHENE XL5423
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83925 PLASTIC PETROTHENE XL5461
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83926 PLASTIC PETROTHENE XL5482
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83927 PLASTIC PETROTHENE XL5483
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83928 PLASTIC PETROTHENE XL5484
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83929 PLASTIC PETROTHENE XL5485
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83930 PLASTIC PETROTHENE XL5486
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83931 PLASTIC PETROTHENE XL5487
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83932 PLASTIC PETROTHENE XL7400
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006151 5

Information Handling Services, 2000

83933 PLASTIC PETROTHENE XL7403
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83934 PLASTIC PETROTHENE XL7410
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83935 PLASTIC PETROTHENE XL7411
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83936 PLASTIC PETROTHENE YR190505
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83937 PLASTIC PETROTHENE YR19512
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83938 PLASTIC PETROTHENE YR92126
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83939 PLASTIC PETROTHENE YR92273
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83940 PLASTIC PETROTHENE YR92411
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

68461 PLASTIC PF-000/15T
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68487 PLASTIC PF-10GF/15T
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68485 PLASTIC PF-20GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68462 PLASTIC PF-20GF/15T
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68463 PLASTIC PF-30CF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68460 PLASTIC PF-30GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006152 7 ■

Information Handling Services, 2000

DATE: 12/23/88
NON-METALS BY DESIGNATION

68488 PLASTIC PF-30GF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68486 PLASTIC PF-40GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68011 PLASTIC PFA
MANF: CHEMPLAST
....NO TEST DATA AVAILABLE....

68492 PLASTIC PI 20GF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68467 PLASTIC PI 30GF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68493 PLASTIC PI 40GF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68468 PLASTIC PI-30 CF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68494 PLASTIC PI-40CF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

81657 PLASTIC PI730
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81658 PLASTIC PI740
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81659 PLASTIC PI745
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81660 PLASTIC PI750
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

68469 PLASTIC PK-20GF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68470 PLASTIC PK-40CF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006153 9

Information Handling Services, 2000

68477 PLASTIC PL-20 NCF/000 FCR
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

85208 PLASTIC PLASKON 1960
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85234 PLASTIC PLASKON 1961
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85237 PLASTIC PLASKON 1974
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85244 PLASTIC PLASKON 1985
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85248 PLASTIC PLASKON 2060
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85256 PLASTIC PLASKON 2061
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85259 PLASTIC PLASKON 3100
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85264 PLASTIC PLASKON 3100-7150
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85268 PLASTIC PLASKON 3100LS
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85272 PLASTIC PLASKON 3130
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85275 PLASTIC PLASKON 3200
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85279 PLASTIC PLASKON 3200LS
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85281 PLASTIC PLASKON 3200SF
MANF: PLASKON
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006154 0 ■

Information Handling Services, 2000

85286 PLASTIC PLASKON 3300
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85288 PLASTIC PLASKON 3300S
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85290 PLASTIC PLASKON 3300SH
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85292 PLASTIC PLASKON 4020
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85294 PLASTIC PLASKON 5000
MANF: PLASKON
....NO TEST DATA AVAILABLE....

85296 PLASTIC PLASKON 5000-7097
MANF: PLASKON
....NO TEST DATA AVAILABLE....

62095 PLASTIC PLASTAFLEX SCPP2500CB GID: EIXXXX
MANF: PLASTIC TRADING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5			00.01	04.20	T MOD
X	1	023.8	014.5			00.01	04.10	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00015.71	

83252 PLASTIC PLASTALLOY J-1505/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83253 PLASTIC PLASTALLOY J-1505/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83254 PLASTIC PLASTALLOY J-1505/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

69740 PLASTIC PLASTIC STEEL PUTTY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

68874 PLASTIC PLASTOLEIN 9050
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68875 PLASTIC PLASTOLEIN 9058
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006155 2

68876 PLASTIC PLASTOLEIN 9065
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68877 PLASTIC PLASTOLEIN 907
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68879 PLASTIC PLASTOLEIN 9091
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68881 PLASTIC PLASTOLEIN 9215
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68882 PLASTIC PLASTOLEIN 9232
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE:...

68880 PLASTIC PLASTOLEIN 9250
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68878 PLASTIC PLASTOLEIN 9404
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68883 PLASTIC PLASTOLEIN 9717
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68884 PLASTIC PLASTOLEIN 9720
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68885 PLASTIC PLASTOLEIN 9731
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68886 PLASTIC PLASTOLEIN 9752
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68887 PLASTIC PLASTOLEIN 9756
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68888 PLASTIC PLASTOLEIN 9761
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68889 PLASTIC PLASTOLEIN 9762
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006156 4

Information Handling Services, 2000

68890 PLASTIC PLASTOLEIN 9765
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68891 PLASTIC PLASTOLEIN 9776
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68892 PLASTIC PLASTOLEIN 9783
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68893 PLASTIC PLASTOLEIN 9789
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

68894 PLASTIC PLASTOLEIN 9790
MANF: EMERY CHEMICALS
....NO TEST DATA AVAILABLE....

85297 PLASTIC PLENCO 00713
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85298 PLASTIC PLENCO 00714
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85299 PLASTIC PLENCO 00732
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85300 PLASTIC PLENCO 00755
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85301 PLASTIC PLENCO 00757
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85302 PLASTIC PLENCO 01500
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85230 PLASTIC PLENCO 01505
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85232 PLASTIC PLENCO 01510
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85238 PLASTIC PLENCO 01529
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F
9999942 0006157 6
Information Handling Services, 2000

85240 PLASTIC PLENCO 01530
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85241 PLASTIC PLENCO 01535
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85243 PLASTIC PLENCO 01580
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85245 PLASTIC PLENCO 01581
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85246 PLASTIC PLENCO 02000
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85249 PLASTIC PLENCO 02300
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85250 PLASTIC PLENCO 023008
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85252 PLASTIC PLENCO 02360
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85254 PLASTIC PLENCO 02408
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85257 PLASTIC PLENCO 02482
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85261 PLASTIC PLENCO 02535
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85263 PLASTIC PLENCO 02567
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85266 PLASTIC PLENCO 02571
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85270 PLASTIC PLENCO 02929
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006158 8

Information Handling Services, 2000

85273 PLASTIC PLENCO 02957
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85277 PLASTIC PLENCO 03343
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85282 PLASTIC PLENCO 03509
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85283 PLASTIC PLENCO 03557
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85284 PLASTIC PLENCO 03597
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85285 PLASTIC PLENCO 04002
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85287 PLASTIC PLENCO 04300
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85289 PLASTIC PLENCO 04301
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85291 PLASTIC PLENCO 04304
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85293 PLASTIC PLENCO 04309
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85295 PLASTIC PLENCO 04349
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85165 PLASTIC PLENCO 04400
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85167 PLASTIC PLENCO 04414
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85171 PLASTIC PLENCO 04466
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006159 T

Information Handling Services, 2000

85177 PLASTIC PLENCO 04485
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85179 PLASTIC PLENCO 04527
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85182 PLASTIC PLENCO 04548
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85184 PLASTIC PLENCO 04568
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85187 PLASTIC PLENCO 05115
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85190 PLASTIC PLENCO 05118
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85192 PLASTIC PLENCO 06201
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85194 PLASTIC PLENCO 06203
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85206 PLASTIC PLENCO 06205
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85196 PLASTIC PLENCO 06305
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85209 PLASTIC PLENCO 06343
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85210 PLASTIC PLENCO 06553
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85211 PLASTIC PLENCO 06554
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85212 PLASTIC PLENCO 06582/MX582
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006160 6 ■

Information Handling Services, 2000

85213 PLASTIC PLENCO 07002
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85214 PLASTIC PLENCO 07080
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85215 PLASTIC PLENCO 07200
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85216 PLASTIC PLENCO 07202
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85217 PLASTIC PLENCO 07203
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85219 PLASTIC PLENCO 07307
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85220 PLASTIC PLENCO 07321
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85222 PLASTIC PLENCO 07368
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85223 PLASTIC PLENCO 07417
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85225 PLASTIC PLENCO 07467
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85227 PLASTIC PLENCO 07476
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85228 PLASTIC PLENCO 07487
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85129 PLASTIC PLENCO 07500
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85132 PLASTIC PLENCO 07502
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006161 8 ■

Information Handling Services, 2000

85135 PLASTIC PLENCO 07507
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85138 PLASTIC PLENCO 07523
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85139 PLASTIC PLENCO 07552
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85142 PLASTIC PLENCO 07579
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85145 PLASTIC PLENCO CELLULOSE-FILLED ALKYD
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85150 PLASTIC PLENCO COPOLYMER ELECTRICAL
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85155 PLASTIC PLENCO ELECTRICAL AND ELECTRONIC ALKYD
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85160 PLASTIC PLENCO ELECTRICAL MOLDING COMPOUND
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

85163 PLASTIC PLENCO GENERAL PURPOSE ALKYD
MANF: PLASTIC ENGINEERING
....NO TEST DATA AVAILABLE....

20059 PLASTIC PLEXIGLASS 2 UVA GID: DTAKXX
MANF: ROHM & HAAS
SPEC: MIL-P-5425

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.57	.00	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.10	

82507 PLASTIC PLEXIGLASS 2-UVT
MANF: ROHM & HAAS
....NO TEST DATA AVAILABLE....

00298 PLASTIC PLEXIGLASS 55 GID: DTAKXX
MANF: GULF WANDES
ROHM & HAAS
SPEC: MIL-P-8184

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.490			00.90	NONE
A	1	023.8	014.5	0.490			03.40	SMALL
A	2	023.8	014.5	0.244			00.90	NONE
A	1	023.8	014.5	0.244			04.70	SMALL
A	2	023.8	014.5	0.742		00.00	00.00	NONE
A	1	023.8	014.5	0.742			03.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F ■ 9999942 0006162 T ■

Information Handling Services, 2000

00298 PLASTIC PLEXIGLASS 55 (cont)

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	030.0	010.0	0.233		00.02	12.00	T NONE										
X	1	030.0	010.0	0.233		00.06	12.00	T MOD										

69916 PLASTIC PLEXIGLASS DR100 GID: DTAKXX

MANF: ROHM & HAAS

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	121.07	

69516 PLASTIC PLEXIGLASS G AND 2 UVA

MANF: GULF WANDES

....NO TEST DATA AVAILABLE....

82506 PLASTIC PLEXIGLASS G-UVT

MANF: ROHM & HAAS

....NO TEST DATA AVAILABLE....

06008 PLASTIC PLEXIGLASS GM2064 GRAY GID: DUAKXX

MANF: ROHM & HAAS SPEC: LP 391 T1

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	023.8	014.5	0.125			01.20	NONE	No test data		No test data							
C	1	023.8	014.5	0.125		00.08	12.00	T SMALL										
I	1	025.9	014.3	0.117		00.11	12.00	T NONE										
I	1	030.0	010.0	0.118		00.11	12.00	T NONE										
X	2	030.0	010.0	0.118		00.09	12.00	T MOD										
X	1	030.0	010.0	0.118		0.1	12.00	T LARGE										

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	2.7E-6	.76	.01	.32		A	V	00020.09	

69517 PLASTIC PLEXIGLASS K

MANF: GULF WANDES

....NO TEST DATA AVAILABLE....

82508 PLASTIC PLEXIGLASS MC

MANF: ROHM & HAAS

....NO TEST DATA AVAILABLE....

69753 PLASTIC PLUMB REPAIR PUTTY

MANF: DEVCON CORP

....NO TEST DATA AVAILABLE....

81646 PLASTIC POCAN B1505

MANF: MOBAY CHEMICAL

....NO TEST DATA AVAILABLE....

81647 PLASTIC POCAN B3225

MANF: MOBAY CHEMICAL

....NO TEST DATA AVAILABLE....

81648 PLASTIC POCAN B3235

MANF: MOBAY CHEMICAL

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006163 1

81649 PLASTIC POCAN B4225
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81650 PLASTIC POCAN B4235
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

81651 PLASTIC POCAN S1506
MANF: MOBAY CHEMICAL
....NO TEST DATA AVAILABLE....

85115 PLASTIC POLIFIL C-20
MANF: POLIFIL
....NO TEST DATA AVAILABLE....

85112 PLASTIC POLIFIL C-40
MANF: POLIFIL
....NO TEST DATA AVAILABLE....

85109 PLASTIC POLIFIL CAS-40
MANF: POLIFIL
....NO TEST DATA AVAILABLE....

85106 PLASTIC POLIFIL HM20
MANF: POLIFIL
....NO TEST DATA AVAILABLE....

85104 PLASTIC POLIFIL HM40
MANF: POLIFIL
....NO TEST DATA AVAILABLE....

85101 PLASTIC POLIFIL M20
MANF: POLIFIL
....NO TEST DATA AVAILABLE....

85098 PLASTIC POLIFIL M40
MANF: POLIFIL
....NO TEST DATA AVAILABLE....

85096 PLASTIC POLIFIL RMC-20
MANF: POLIFIL
....NO TEST DATA AVAILABLE....

85093 PLASTIC POLIFIL RMC-40
MANF: POLIFIL
....NO TEST DATA AVAILABLE....

85090 PLASTIC POLIFIL RMT-20
MANF: POLIFIL
....NO TEST DATA AVAILABLE....

85087 PLASTIC POLIFIL RMT-40
MANF: POLIFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006164 3 ■

Information Handling Services, 2000

85084 PLASTIC POLIFIL T-20
MANF: POLIFIL
....NO TEST DATA AVAILABLE....

85078 PLASTIC POLIFIL T-40
MANF: POLIFIL
....NO TEST DATA AVAILABLE....

67999 PLASTIC POLY EMULSION 10 N30
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67993 PLASTIC POLY EMULSION 121 N30
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67992 PLASTIC POLY EMULSION 153 N35
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67983 PLASTIC POLY EMULSION 261 A35
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67991 PLASTIC POLY EMULSION 316 N30
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67985 PLASTIC POLY EMULSION 325 N35
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67986 PLASTIC POLY EMULSION 330 N35
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

68001 PLASTIC POLY EMULSION 371 N30
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67987 PLASTIC POLY EMULSION 392 A25
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67990 PLASTIC POLY EMULSION 392 C30
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67988 PLASTIC POLY EMULSION 392 LE30
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67989 PLASTIC POLY EMULSION 392 N25
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006165 5

Information Handling Services, 2000

67984 PLASTIC POLY EMULSION 392 N35
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

68002 PLASTIC POLY EMULSION 43 N40
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67996 PLASTIC POLY EMULSION 540 A25
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67994 PLASTIC POLY EMULSION 540 N30
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67995 PLASTIC POLY EMULSION 540 N40
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67997 PLASTIC POLY EMULSION 629 A30
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

67998 PLASTIC POLY EMULSION 629 N04
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

68000 PLASTIC POLY EMULSION 656 A25
MANF: CHEMICAL CORPORATION OF AMERICA
....NO TEST DATA AVAILABLE....

69735 PLASTIC POLY-CLEAR
MANF: TRANSENE
....NO TEST DATA AVAILABLE....

80534 PLASTIC POLY-GLAZ SHEET
MANF: AEROMAT PLASTICS
....NO TEST DATA AVAILABLE....

69789 PLASTIC POLYACETAL HOMOPOLYMER
MANF: CADILLAC PLASTICS
....NO TEST DATA AVAILABLE....

83255 PLASTIC POLYCARBAFIL F-50/20/FR
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83256 PLASTIC POLYCARBAFIL G-50/20/FR
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83257 PLASTIC POLYCARBAFIL G-50/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F
9999942 0006166 7

Information Handling Services, 2000

83259 PLASTIC POLYCARBAFIL J-5/30/FR
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83258 PLASTIC POLYCARBAFIL J-50/20/FR
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83260 PLASTIC POLYCARBAFIL J-50/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83262 PLASTIC POLYCARBAFIL J-50/M/5/CE/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83263 PLASTIC POLYCARBAFIL J-54/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83266 PLASTIC POLYCARBAFIL/FOAM F-50/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83269 PLASTIC POLYCARBAFIL/FOAM F-50/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83272 PLASTIC POLYCARBAFIL/FOAM F-50/20 LONG GLASS
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83274 PLASTIC POLYCARBAFIL/FOAM F-50/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83276 PLASTIC POLYCARBAFIL/FOAM F-50/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

68558 PLASTIC POLYCARBONATE
MANF: DIXON INDUSTRIES

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.12	.02	.00	

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

68559 PLASTIC POLYCARBONATE 20% GLASS
MANF: DIXON INDUSTRIES

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.14	.01	.00	

ODOR		TOXICITY	
RT	RT WEIGHT	CURE	
No test data			

82134 PLASTIC POLYDAP 6120
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006167 9

Information Handling Services, 2000

82135 PLASTIC POLYDAP 6120F
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82136 PLASTIC POLYDAP 6130
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82137 PLASTIC POLYDAP 6130F
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82138 PLASTIC POLYDAP 6160
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82139 PLASTIC POLYDAP 6220
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

82140 PLASTIC POLYDAP 6260
MANF: DIELECTRIC POLYMERS
....NO TEST DATA AVAILABLE....

68562 PLASTIC POLYETHERSULFONE 30% CF
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68561 PLASTIC POLYETHERSULFONE 30% GLASS
MANF: DIXON INDUSTRIES

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.82	.03	.00	SEE TEST REPORT	No test data		

80773 PLASTIC POLYETHYLENE (LINEAR)
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

80327 PLASTIC POLYFLAM RCP762
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80328 PLASTIC POLYFLAM RCP770C
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80329 PLASTIC POLYFLAM RHD260ND (E)
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80330 PLASTIC POLYFLAM RHD260ND RLP426
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80331 PLASTIC POLYFLAM RMS424
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F
9999942 0006168 0
Information Handling Services, 2000

DATE: 12/23/88
NON-METALS BY DESIGNATION

80332 PLASTIC POLYFLAM RMS424E
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80333 PLASTIC POLYFLAM RPP1021
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80334 PLASTIC POLYFLAM RPP1058
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80335 PLASTIC POLYFLAM RPP1062C
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80336 PLASTIC POLYFLAM RPP1174
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80337 PLASTIC POLYFLAM RPP932
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80338 PLASTIC POLYFLAM RPP958
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80339 PLASTIC POLYFLAM RPP958E
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80340 PLASTIC POLYFLAM RPP982
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80341 PLASTIC POLYFLAM RPP985
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80342 PLASTIC POLYFLAM RS425C3
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80343 PLASTIC POLYFORT FPP1006
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80344 PLASTIC POLYFORT FPP1007
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80345 PLASTIC POLYFORT FPP1182
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006169 2

Information Handling Services, 2000

80346 PLASTIC POLYFORT FPP1200
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80347 PLASTIC POLYFORT FPP1223
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80348 PLASTIC POLYFORT FPP1227
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80349 PLASTIC POLYFORT FPP1237
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80350 PLASTIC POLYFORT FPP1244
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80351 PLASTIC POLYFORT FPP1245
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80352 PLASTIC POLYFORT FPP1257
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80353 PLASTIC POLYFORT FPP1272
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80354 PLASTIC POLYFORT FPP1309
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80355 PLASTIC POLYFORT FPP1310
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80356 PLASTIC POLYFORT FPP1337
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80357 PLASTIC POLYFORT FPP1345
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80358 PLASTIC POLYFORT FPP1383
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80359 PLASTIC POLYFORT FPP1488
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006170 9 ■

Information Handling Services, 2000

80360 PLASTIC POLYFORT FPP1494
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80361 PLASTIC POLYFORT FPP1512
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80362 PLASTIC POLYFORT FPP1564
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80363 PLASTIC POLYFORT FPP1578
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80364 PLASTIC POLYFORT FPP1607
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80365 PLASTIC POLYFORT FPP1608
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80366 PLASTIC POLYFORT FPP1609
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80367 PLASTIC POLYFORT FPP1611
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80368 PLASTIC POLYFORT FPP1612
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80369 PLASTIC POLYFORT FPP1650
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80370 PLASTIC POLYFORT FPP1651
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80371 PLASTIC POLYFORT FPP1652
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80372 PLASTIC POLYFORT FPP1653
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80373 PLASTIC POLYFORT FPP1654
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006171 0 ■

Information Handling Services, 2000

80374 PLASTIC POLYFORT FPP1666
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80375 PLASTIC POLYFORT PP1531
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80376 PLASTIC POLYFORT PP1549
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80377 PLASTIC POLYFORT PP828
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80378 PLASTIC POLYFORT PP829
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80379 PLASTIC POLYMAN 506
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80380 PLASTIC POLYMAN 507
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80381 PLASTIC POLYMAN 508
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80382 PLASTIC POLYMAN 509
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80383 PLASTIC POLYMAN 510
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80384 PLASTIC POLYMAN 511
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80385 PLASTIC POLYMAN 526
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80386 PLASTIC POLYMAN 551
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80387 PLASTIC POLYMAN 552
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006172 2 ■

Information Handling Services, 2000

80388 PLASTIC POLYMAN 554
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80389 PLASTIC POLYMAN 558
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

82379 PLASTIC POLYMETHYLPENTENE DX 845
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

80609 PLASTIC POLYMIST F-5
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

80610 PLASTIC POLYMIST F-510
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

80611 PLASTIC POLYMIST F-5A
MANF: ALLIED CHEMICAL
....NO TEST DATA AVAILABLE....

69556 PLASTIC POLYPENCE TFE
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

80535 PLASTIC POLYPENCO 101 (NYLON 6/6)
MANF: AEROMAT PLASTICS
....NO TEST DATA AVAILABLE....

80536 PLASTIC POLYPENCO 11
MANF: AEROMAT PLASTICS
....NO TEST DATA AVAILABLE....

80537 PLASTIC POLYPENCO 12
MANF: AEROMAT PLASTICS
....NO TEST DATA AVAILABLE....

84401 PLASTIC POLYPENCO 25% GLASS FILLED TFE
MANF: CURBELL
....NO TEST DATA AVAILABLE....

84402 PLASTIC POLYPENCO FLUOROSINT 207
MANF: CURBELL
....NO TEST DATA AVAILABLE....

84403 PLASTIC POLYPENCO FLUOROSINT 500
MANF: CURBELL
....NO TEST DATA AVAILABLE....

85242 PLASTIC POLYPENCO PTFE FLUOROCARBON
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006173 4

84404 PLASTIC POLYPENCO TFE FLUOROCARBON
MANF: CURBELL
....NO TEST DATA AVAILABLE....

69559 PLASTIC POLYPENCO TR-1
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

68564 PLASTIC POLYPROPYLENE
MANF: DIXON INDUSTRIES
GULF WANDES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.96	.07	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

68565 PLASTIC POLYPROPYLENE 10% GLASS
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

82001 PLASTIC POLYPROPYLENE 20% CALCIUM CARBONATE FILLED
MANF: HAMMOND PLASTICS
....NO TEST DATA AVAILABLE....

82002 PLASTIC POLYPROPYLENE 20% TALC FILLED
MANF: HAMMOND PLASTICS
....NO TEST DATA AVAILABLE....

68566 PLASTIC POLYPROPYLENE 30% GLASS
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

82003 PLASTIC POLYPROPYLENE 40% CALCIUM CARBONATE FILLED
MANF: HAMMOND PLASTICS
....NO TEST DATA AVAILABLE....

82004 PLASTIC POLYPROPYLENE 40% TALC FILLED
MANF: HAMMOND PLASTICS
....NO TEST DATA AVAILABLE....

81441 PLASTIC POLYPROPYLENE 4231A
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

69992 PLASTIC POLYPROPYLENE FILTRETE G108
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.046			05.50	SMALL
C	1	030.0	010.0	0.046		00.50	10.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80774 PLASTIC POLYPROPYLENE HOMOPOLYMER
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

80776 PLASTIC POLYPROPYLENE HOMOPOLYMER V-2
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006174 6

Information Handling Services, 2000

80775 PLASTIC POLYPROPYLENE HOMOPOLYMER V-O
MANF: ASHLAND CHEM
....NO TEST DATA AVAILABLE....

85251 PLASTIC POLYSAR 101
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

85253 PLASTIC POLYSAR 103
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

85255 PLASTIC POLYSAR 200
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

85258 PLASTIC POLYSAR 202
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

85260 PLASTIC POLYSAR 203
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

85262 PLASTIC POLYSAR 205
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

85265 PLASTIC POLYSAR 208
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

85267 PLASTIC POLYSAR 220
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

85269 PLASTIC POLYSAR 2220
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

85271 PLASTIC POLYSAR 2400
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

85274 PLASTIC POLYSAR 3350
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

85276 PLASTIC POLYSAR 415
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

85278 PLASTIC POLYSAR 4220
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006175 8

Information Handling Services, 2000

85280 PLASTIC POLYSAR 4300
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

82168 PLASTIC POLYSAR 520
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

82169 PLASTIC POLYSAR 5220
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

82170 PLASTIC POLYSAR 525
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

82171 PLASTIC POLYSAR 555
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

82172 PLASTIC POLYSAR 777
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

82173 PLASTIC POLYSAR 9720
MANF: POLYSAR
....NO TEST DATA AVAILABLE....

80867 PLASTIC POLYSTYROL 143E
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80868 PLASTIC POLYSTYROL 144C
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

85363 PLASTIC POLYSTYROL 158K
MANF: BASF STRUCTURAL MATERIALS
PREMIX INC
....NO TEST DATA AVAILABLE....

80869 PLASTIC POLYSTYROL 158KG6
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80871 PLASTIC POLYSTYROL 165H
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80872 PLASTIC POLYSTYROL 168H
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80873 PLASTIC POLYSTYROL 427D
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006176 T

Information Handling Services, 2000

80874 PLASTIC POLYSTYROL 432B
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80875 PLASTIC POLYSTYROL 454C
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80876 PLASTIC POLYSTYROL 454H
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80877 PLASTIC POLYSTYROL 456M
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80878 PLASTIC POLYSTYROL 466I
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80879 PLASTIC POLYSTYROL 472C
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80880 PLASTIC POLYSTYROL 473D
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80881 PLASTIC POLYSTYROL 475K
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80882 PLASTIC POLYSTYROL 476L
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80883 PLASTIC POLYSTYROL KR2711
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80884 PLASTIC POLYSTYROL KR2751
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80885 PLASTIC POLYSTYROL KR2791
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80886 PLASTIC POLYSTYROL SB2710
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

68556 PLASTIC POLYSULFONE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006177 1

Information Handling Services, 2000

68557 PLASTIC POLYSULFONE 30% CF
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

61618 PLASTIC POLYSULFONE P1700 GID: DKCIXX
MANF: UNION CARBIDE
WESTLAKE PLASTICS CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	088.0	0.060		00.20	10.90	MOD
A	1	020.9	014.7	0.123			00.90	NONE
A	1	023.8	014.5	0.097			01.50	SMALL
A	1	025.9	014.3	0.123			01.40	NONE
A	1	030.0	010.0	0.123			01.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	500	25	200	0.064	00	20
I	PNEU	500		200	0.064	0	3
B	PNEU	600		200	0.064	0	20
X	PNEU	700		200	0.064	1	8
X	PNEU	700		200	0.064	1	80

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.25	.01	.00	

ODOR

RT	RT	WEIGHT	CURE
A	K	22.568	

TOXICITY

05209 PLASTIC POLYSULFONE P1700/P3500 GID: EXCIXX
MANF: UNION CARBIDE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.086			00.90	SMALL

FSC

RT	FLUID NAME
A	AMMONIA

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.09	.02	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

80390 PLASTIC POLYTROPE TPP1201
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80391 PLASTIC POLYTROPE TPP293
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80392 PLASTIC POLYTROPE TPP300
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80393 PLASTIC POLYTROPE TPP309
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80394 PLASTIC POLYTROPE TPP313
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80395 PLASTIC POLYTROPE TPP317
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80396 PLASTIC POLYTROPE TPP318
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80397 PLASTIC POLYTROPE TPP319
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006178 3

80398 PLASTIC POLYTROPE TPP320
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80399 PLASTIC POLYTROPE TPP334
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80400 PLASTIC POLYTROPE TPP336
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80401 PLASTIC POLYTROPE TPP337
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80402 PLASTIC POLYTROPE TPP338
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80403 PLASTIC POLYTROPE TPP341
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80404 PLASTIC POLYTROPE TPP377
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80405 PLASTIC POLYTROPE TPP393
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80406 PLASTIC POLYTROPE TPP394
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80407 PLASTIC POLYTROPE TPP402
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80408 PLASTIC POLYTROPE TPP403
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80409 PLASTIC POLYTROPE TPP408
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80410 PLASTIC POLYTROPE TPP409
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80411 PLASTIC POLYTROPE TPP414
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006179 5 ■

Information Handling Services, 2000

80412 PLASTIC POLYTROPE TPP420
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80413 PLASTIC POLYTROPE TPP421
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80414 PLASTIC POLYTROPE TPP425
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80415 PLASTIC POLYTROPE TPP427
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80416 PLASTIC POLYTROPE TPP433
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80417 PLASTIC POLYTROPE TPP442
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80418 PLASTIC POLYTROPE TPP443
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80419 PLASTIC POLYTROPE TPP444
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80420 PLASTIC POLYTROPE TPP445
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80421 PLASTIC POLYTROPE TPP446
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80422 PLASTIC POLYTROPE TPP447
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80423 PLASTIC POLYVIN 4507
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80424 PLASTIC POLYVIN 5004
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80425 PLASTIC POLYVIN 5023
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006180 1 ■

Information Handling Services, 2000

80426 PLASTIC POLYVIN 5514
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80427 PLASTIC POLYVIN 5802
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80428 PLASTIC POLYVIN 5813
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80429 PLASTIC POLYVIN 5819
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80430 PLASTIC POLYVIN 5824
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80431 PLASTIC POLYVIN 6110
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80432 PLASTIC POLYVIN 6415
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80433 PLASTIC POLYVIN 6424
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80434 PLASTIC POLYVIN 6588
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80435 PLASTIC POLYVIN 6614
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80436 PLASTIC POLYVIN 6618
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80437 PLASTIC POLYVIN 6713
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80438 PLASTIC POLYVIN 6820
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80439 PLASTIC POLYVIN 6825
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

80440 PLASTIC POLYVIN 6837
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80441 PLASTIC POLYVIN 7112
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80442 PLASTIC POLYVIN 7125
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80443 PLASTIC POLYVIN 7180
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80444 PLASTIC POLYVIN 7280
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80445 PLASTIC POLYVIN 7427
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80446 PLASTIC POLYVIN 7522
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80447 PLASTIC POLYVIN 7532
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80448 PLASTIC POLYVIN 7601
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80449 PLASTIC POLYVIN 7709
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80450 PLASTIC POLYVIN 7856
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80451 PLASTIC POLYVIN 7911
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80452 PLASTIC POLYVIN 8058
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80453 PLASTIC POLYVIN 8101
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006182 5

Information Handling Services, 2000

80454 PLASTIC POLYVIN 8110
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80455 PLASTIC POLYVIN 8111
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80456 PLASTIC POLYVIN 8124
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80457 PLASTIC POLYVIN 8125
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80458 PLASTIC POLYVIN 8222
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80459 PLASTIC POLYVIN 8380
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80460 PLASTIC POLYVIN 8384
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80461 PLASTIC POLYVIN 8428
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80462 PLASTIC POLYVIN 8540
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80463 PLASTIC POLYVIN 8546
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80464 PLASTIC POLYVIN 8612
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80465 PLASTIC POLYVIN 8803
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80466 PLASTIC POLYVIN 8813
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80467 PLASTIC POLYVIN 8819
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006183 7

Information Handling Services, 2000

80468 PLASTIC POLYVIN 8820
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80469 PLASTIC POLYVIN 8822
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80470 PLASTIC POLYVIN 8835
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80471 PLASTIC POLYVIN 9009
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80472 PLASTIC POLYVIN 9044
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80473 PLASTIC POLYVIN 9108
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80474 PLASTIC POLYVIN 9226
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80475 PLASTIC POLYVIN 9400
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

80476 PLASTIC POLYVIN 9533
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

60137 PLASTIC POLYVINYL CHLORIDE (PVC) GID: DKHCXX
MANF: SPEC: ASTM D1755
....NO TEST DATA AVAILABLE....

83953 PLASTIC PP-C2TF4
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83954 PLASTIC PP-C3CC4
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83955 PLASTIC PP-C3TF2
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83956 PLASTIC PP-C4IM-V
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F
9999942 0006184 9
Information Handling Services, 2000

DATE: 12/23/88
NON-METALS BY DESIGNATION

83957 PLASTIC PP-C5CC2
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83958 PLASTIC PP-C6CC4
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83959 PLASTIC PP-H1CC1
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83960 PLASTIC PP-H2CC2
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83961 PLASTIC PP-H2LTF4
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83962 PLASTIC PP-H2MFQ3
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83963 PLASTIC PP-H2MFQ4
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83964 PLASTIC PP-H2MFS3
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83965 PLASTIC PP-H2MFS4
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83966 PLASTIC PP-H2TF2
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83967 PLASTIC PP-H3MF2
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83968 PLASTIC PP-H3MF05
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83969 PLASTIC PP-H4CG4
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83970 PLASTIC PP-H4TF3
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006185 0

Information Handling Services, 2000

83971 PLASTIC PP-H6CC4
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83972 PLASTIC PP-H7CC4
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83973 PLASTIC PP-HFG1
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83974 PLASTIC PP-HFG2
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83975 PLASTIC PP-HFG3
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83976 PLASTIC PP-HFGC2
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83977 PLASTIC PP-HFGC3
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83978 PLASTIC PP-HIFR
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

83979 PLASTIC PP-TFFR2
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

68822 PLASTIC PP11512A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68824 PLASTIC PP11530V
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68821 PLASTIC PP1154A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68796 PLASTIC PP11B12A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68798 PLASTIC PP11B30V
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006186 2 ■

Information Handling Services, 2000

68795 PLASTIC PP11C8A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68823 PLASTIC PP11N12A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68797 PLASTIC PP11S20U
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68828 PLASTIC PP13510A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68827 PLASTIC PP13N5A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68801 PLASTIC PP13R9A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68802 PLASTIC PP13T10A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68830 PLASTIC PP1452A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68804 PLASTIC PP1454A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68831 PLASTIC PP1455A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68805 PLASTIC PP1456A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68829 PLASTIC PP14B12A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68803 PLASTIC PP14C5A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68832 PLASTIC PP1752A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

68806 PLASTIC PP1753A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68833 PLASTIC PP1754A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68807 PLASTIC PP1756A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68808 PLASTIC PP17C20A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68835 PLASTIC PP17C20A (XO-70/XO-76)
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68834 PLASTIC PP17C6A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68809 PLASTIC PP1852A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68836 PLASTIC PP1853A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68810 PLASTIC PP1856A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

83952 PLASTIC PP1MT3
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

68837 PLASTIC PP2352
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68811 PLASTIC PP2352A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68838 PLASTIC PP23B2
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68812 PLASTIC PP23B2A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006188 6 ■

Information Handling Services, 2000

68839 PLASTIC PP23M2
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68799 PLASTIC PP23M2CS219
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68813 PLASTIC PP23T2A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68840 PLASTIC PP24T2A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68790 PLASTIC PP3152A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68818 PLASTIC PP31530V
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68817 PLASTIC PP3153A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68791 PLASTIC PP3154A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68792 PLASTIC PP4152A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68820 PLASTIC PP4154A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68819 PLASTIC PP41E2
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68793 PLASTIC PP41E4
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68794 PLASTIC PP41J7A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68826 PLASTIC PP43J4A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006189 8

Information Handling Services, 2000

68800 PLASTIC PP4453A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68563 PLASTIC PPO
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68495 PLASTIC PR-20CF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

82174 PLASTIC PREMIGLAS 1000 BMC GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82175 PLASTIC PREMIGLAS 1100 BMC LS 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82176 PLASTIC PREMIGLAS 1100 BMC-LS 22% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82177 PLASTIC PREMIGLAS 1100 BMC-LS 30%GLAS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82178 PLASTIC PREMIGLAS 1100-05
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82179 PLASTIC PREMIGLAS 1100-10
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82180 PLASTIC PREMIGLAS 1100-15
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82181 PLASTIC PREMIGLAS 1200 SMC-LS 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82182 PLASTIC PREMIGLAS 1200 SMC-LS 22% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82183 PLASTIC PREMIGLAS 1200 SMC-LS 30% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82184 PLASTIC PREMIGLAS 2000 BMC 10% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006190 4

Information Handling Services, 2000

82185 PLASTIC PREMIGLAS 2000 BMC 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82186 PLASTIC PREMIGLAS 2000 BMC 22% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82187 PLASTIC PREMIGLAS 2000 BMC 30% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82190 PLASTIC PREMIGLAS 2003 22% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82188 PLASTIC PREMIGLAS 2003 BMC 10% GLASS
....NO TEST DATA AVAILABLE....

82189 PLASTIC PREMIGLAS 2003 BMC 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82191 PLASTIC PREMIGLAS 2003 BMC 30% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82192 PLASTIC PREMIGLAS 2100 BMC-LS 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82193 PLASTIC PREMIGLAS 2100 BMC-LS 22% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82194 PLASTIC PREMIGLAS 2100 BMC-LS 30% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82195 PLASTIC PREMIGLAS 2103 BMC-LS 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82196 PLASTIC PREMIGLAS 2103 BMC-LS 22% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82197 PLASTIC PREMIGLAS 2103 BMC-LS 30% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82198 PLASTIC PREMIGLAS 2200 SMC-LS 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82199 PLASTIC PREMIGLAS 2200 SMC-LS 22% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006191 6

Information Handling Services, 2000

82200 PLASTIC PREMIGLAS 2200 SMC-LS 30% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82201 PLASTIC PREMIGLAS 2203 SMC-LS 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82202 PLASTIC PREMIGLAS 2203 SMC-LS 22% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82203 PLASTIC PREMIGLAS 2203 SMC-LS 30% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82204 PLASTIC PREMIGLAS 3000 BMC 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82205 PLASTIC PREMIGLAS 3000 BMC 30% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82206 PLASTIC PREMIGLAS 3100 BMC-LS 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82207 PLASTIC PREMIGLAS 3100 BMC-LS 22% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82208 PLASTIC PREMIGLAS 3100 BMC-LS 30% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82209 PLASTIC PREMIGLAS 3140 MSG
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82210 PLASTIC PREMIGLAS 3200 SMC-LS 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82211 PLASTIC PREMIGLAS 3200 SMC-LS 22% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82212 PLASTIC PREMIGLAS 3200 SMC-LS 30% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82213 PLASTIC PREMIGLAS 4000 BMC 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006192 8

Information Handling Services, 2000

82214 PLASTIC PREMIGLAS 4000 BMC 22% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82215 PLASTIC PREMIGLAS 4000 BMC 30% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82216 PLASTIC PREMIGLAS 4100 BMC-LS 22% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82217 PLASTIC PREMIGLAS 4100 BMC-LS 30% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82218 PLASTIC PREMIGLAS 4200 SMC-LS 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82219 PLASTIC PREMIGLAS 4200 SMC-LS 22% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82220 PLASTIC PREMIGLAS 4200 SMC-LS 30% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82221 PLASTIC PREMIGLAS 7100 BMC 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82222 PLASTIC PREMIGLAS 7100 BMC 22% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82223 PLASTIC PREMIGLAS 7200 SMC
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82224 PLASTIC PREMIGLAS 7200 SMC 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82225 PLASTIC PREMIGLAS 7200 SMC 22% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82226 PLASTIC PREMIGLAS 7200 SMC 30% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82227 PLASTIC PREMIGLAS 8140 TMC
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006193 T ■

82228 PLASTIC PREMIGLAS 8200 SMC
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82229 PLASTIC PREMIGLAS BMC-EMI
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82230 PLASTIC PREMIGLAS BMC-ESD
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82231 PLASTIC PREMIGLAS EPOXY 1200E 50% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82232 PLASTIC PREMIGLAS EPOXY 1200E 65% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82233 PLASTIC PREMIGLAS HSMC
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82234 PLASTIC PREMIGLAS HSMC 3200 50% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82235 PLASTIC PREMIGLAS SMC-EMI
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82236 PLASTIC PREMIGLAS SMC-ESD
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82237 PLASTIC PREMIGLAS TMC-EMI
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82238 PLASTIC PREMIGLAS TWC-ESD
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82239 PLASTIC PREMIJECT 1100V BMC-LS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82240 PLASTIC PREMIJECT 1140 TMC-LS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82241 PLASTIC PREMIJECT 1140V TMC-LS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006194 1

Information Handling Services, 2000

82242 PLASTIC PREMIJECT 6000 BMC 10% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82243 PLASTIC PREMIJECT 6000 BMC 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82244 PLASTIC PREMIJECT 6000 BMC 20% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82245 PLASTIC PREMIJECT 6000 BMC 5% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82246 PLASTIC PREMIJECT 6100 BMC-LS 10% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82247 PLASTIC PREMIJECT 6100 BMC-LS 15% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82248 PLASTIC PREMIJECT 6100 BMC-LS 20% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

82249 PLASTIC PREMIJECT 6100 BMC-LS 5% GLASS
MANF: PREMIX INC
....NO TEST DATA AVAILABLE....

81046 PLASTIC PREVEX BIA
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81047 PLASTIC PREVEX BJA
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81048 PLASTIC PREVEX BJB
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81049 PLASTIC PREVEX BJC
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81050 PLASTIC PREVEX BJF
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81051 PLASTIC PREVEX BJU
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006195 3

Information Handling Services, 2000

81079 PLASTIC PREVEX HC2
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81052 PLASTIC PREVEX MPF
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81053 PLASTIC PREVEX MPR
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81054 PLASTIC PREVEX MVF
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81055 PLASTIC PREVEX MVP
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81056 PLASTIC PREVEX P2A
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81057 PLASTIC PREVEX P3A
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81058 PLASTIC PREVEX PMA
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81059 PLASTIC PREVEX PQ1
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81060 PLASTIC PREVEX PQA
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81061 PLASTIC PREVEX V2A
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81062 PLASTIC PREVEX V3A
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81063 PLASTIC PREVEX VF1
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81064 PLASTIC PREVEX VFA
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006196 5

Information Handling Services, 2000

81065 PLASTIC PREVEX VGA
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81066 PLASTIC PREVEX VJA
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81067 PLASTIC PREVEX VJB
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81068 PLASTIC PREVEX VK1
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81069 PLASTIC PREVEX VKA
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81070 PLASTIC PREVEX VM1
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81071 PLASTIC PREVEX VMA
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81072 PLASTIC PREVEX VQ1
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81073 PLASTIC PREVEX VQA
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81074 PLASTIC PREVEX W20
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81075 PLASTIC PREVEX W30
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81076 PLASTIC PREVEX W40
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81077 PLASTIC PREVEX W50
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

81078 PLASTIC PREVEX W70
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006197 7

Information Handling Services, 2000

82041 PLASTIC PROFAX 6323
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82042 PLASTIC PROFAX 6331
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82043 PLASTIC PROFAX 6331NW
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82044 PLASTIC PROFAX 6523
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82045 PLASTIC PROFAX 6524
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82046 PLASTIC PROFAX 65F4-2
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82047 PLASTIC PROFAX 65F4-4
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82048 PLASTIC PROFAX 65F5-2
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82049 PLASTIC PROFAX 65F5-4
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82050 PLASTIC PROFAX 6723
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82051 PLASTIC PROFAX 6823
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82052 PLASTIC PROFAX 7523
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82053 PLASTIC PROFAX 75F4-2
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82054 PLASTIC PROFAX 75F4-4
MANF: HERCULES
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F
9999942 0006198 9
Information Handling Services, 2000

82055 PLASTIC PROFAX 75F5-2
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82056 PLASTIC PROFAX 75F5-4
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82057 PLASTIC PROFAX 7623
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82058 PLASTIC PROFAX 7624
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82059 PLASTIC PROFAX 7723
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82060 PLASTIC PROFAX 7823
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82061 PLASTIC PROFAX 8523
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82062 PLASTIC PROFAX 8623
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82063 PLASTIC PROFAX PD064
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82064 PLASTIC PROFAX PD195
MANF: HERCULES
....NO TEST DATA AVAILABLE....

82065 PLASTIC PROFAX SB222PM
MANF: HERCULES
....NO TEST DATA AVAILABLE....

83278 PLASTIC PROFIL G-60/20
MANF: WILSON FIBERFIL

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.17	.04	.00		No test data		

83279 PLASTIC PROFIL G-60/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83281 PLASTIC PROFIL J-60/10/E3
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006199 0

83283 PLASTIC PROFIL J-60/10/E4
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83287 PLASTIC PROFIL J-60/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83289 PLASTIC PROFIL J-60/20/E
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83291 PLASTIC PROFIL J-60/20/E3
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83293 PLASTIC PROFIL J-60/20/E4
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83295 PLASTIC PROFIL J-60/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83296 PLASTIC PROFIL J-60/30/E
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83298 PLASTIC PROFIL J-60/30/ER
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83381 PLASTIC PROFIL J-60/30/FR
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83299 PLASTIC PROFIL J-60/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83301 PLASTIC PROFIL J-60/40/E
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83303 PLASTIC PROFIL J-60/40/E3
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83306 PLASTIC PROFIL J-60/40/ER
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83307 PLASTIC PROFIL J-61/10/WAT
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F
9999942 0006200 3
Information Handling Services, 2000

83309 PLASTIC PROFIL J-61/20/NAT
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83310 PLASTIC PROFIL J-61/30/NAT
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83320 PLASTIC PROFIL J-61/40/NAT
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83321 PLASTIC PROFIL J-62/10/E4
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83322 PLASTIC PROFIL J-62/20/E4
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83323 PLASTIC PROFIL J-62/30/E4
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83324 PLASTIC PROFIL J-62/40/E4
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83325 PLASTIC PROFIL PF-6000
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83326 PLASTIC PROFIL PF-6000/EC
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83327 PLASTIC PROFIL PF-6001
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83328 PLASTIC PROFIL PF-6010
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83329 PLASTIC PROFIL PF-6012
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83330 PLASTIC PROFIL PF-6013
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83331 PLASTIC PROFIL PF6020
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

83333 PLASTIC PROFIL PF6022
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83334 PLASTIC PROFIL PF6023
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83337 PLASTIC PROFIL PF6024
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83340 PLASTIC PROFIL PP-60 FR
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83338 PLASTIC PROFIL PP-60/CC/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83339 PLASTIC PROFIL PP-60/CC/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83342 PLASTIC PROFIL PP-60/TC/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83343 PLASTIC PROFIL PP-60/TC/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83345 PLASTIC PROFIL PP-61/CC/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83347 PLASTIC PROFIL PP-61/CC/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83348 PLASTIC PROFIL PP-61/TC/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83349 PLASTIC PROFIL PP-61/TC/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83353 PLASTIC PROFIL PP-62/MI/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83350 PLASTIC PROFIL PP-62/TC/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006202 7

83352 PLASTIC PROFIL PP-62/TC/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83525 PLASTIC PROFIL/FOAM F-60/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83998 PLASTIC PROLOY HC3
MANF: BORG WARNER
....NO TEST DATA AVAILABLE....

69146 PLASTIC PROPIONATE FORMULA 350 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

81558 PLASTIC PS MX7100A
MANF: MOBIL OIL CORP
....NO TEST DATA AVAILABLE....

68490 PLASTIC PS-10GF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68464 PLASTIC PS-15GF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68491 PLASTIC PS-15GF/000 GR
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68489 PLASTIC PS-20GF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68465 PLASTIC PS-30GF 30% GLASS
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68466 PLASTIC PS-30GF/000 FR
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

84406 PLASTIC PS102-0
MANF: DART INDUSTRIES
....NO TEST DATA AVAILABLE....

84407 PLASTIC PS102-1
MANF: DART INDUSTRIES
....NO TEST DATA AVAILABLE....

84408 PLASTIC PS108-1
MANF: DART INDUSTRIES
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006203 9

Information Handling Services, 2000

84409 PLASTIC PS118-1
MANF: DART INDUSTRIES
....NO TEST DATA AVAILABLE....

81545 PLASTIC PS1400
MANF: MOBIL OIL CORP
....NO TEST DATA AVAILABLE....

84410 PLASTIC PS202
MANF: DART INDUSTRIES
....NO TEST DATA AVAILABLE....

84411 PLASTIC PS208
MANF: DART INDUSTRIES
....NO TEST DATA AVAILABLE....

81546 PLASTIC PS2124
MANF: MOBIL OIL CORP
....NO TEST DATA AVAILABLE....

84412 PLASTIC PS304
MANF: DART INDUSTRIES
....NO TEST DATA AVAILABLE....

84413 PLASTIC PS308
MANF: DART INDUSTRIES
....NO TEST DATA AVAILABLE....

81548 PLASTIC PS3654
MANF: MOBIL OIL CORP
....NO TEST DATA AVAILABLE....

81549 PLASTIC PS3824
MANF: MOBIL OIL CORP
....NO TEST DATA AVAILABLE....

81550 PLASTIC PS4154
MANF: MOBIL OIL CORP
....NO TEST DATA AVAILABLE....

81551 PLASTIC PS4324
MANF: MOBIL OIL CORP
....NO TEST DATA AVAILABLE....

81552 PLASTIC PS4600
MANF: MOBIL OIL CORP
....NO TEST DATA AVAILABLE....

81553 PLASTIC PS5400
MANF: MOBIL OIL CORP
....NO TEST DATA AVAILABLE....

81555 PLASTIC PS8120
MANF: MOBIL OIL CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006204 0 ■

Information Handling Services, 2000

81557 PLASTIC PS9524
MANF: MOBIL OIL CORP
....NO TEST DATA AVAILABLE....

84799 PLASTIC PULSE ENGINEERING RESINS 600
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84803 PLASTIC PULSE ENGINEERING RESINS 710
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84805 PLASTIC PULSE ENGINEERING RESINS 830
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84807 PLASTIC PULSE ENGINEERING RESINS 855
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84809 PLASTIC PULSE ENGINEERING RESINS 869
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84801 PLASTIC PULSE ENGINEERING RSINS 700
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

69522 PLASTIC PVC TYPE I
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

68588 PLASTIC PVDF
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

82519 PLASTIC PWB 14A
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82520 PLASTIC PWB 14A 100% REGIND
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82521 PLASTIC PWB 14A VIRGIN
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82522 PLASTIC PWB 14A VIRGIN WITH 20% REGRIND
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82523 PLASTIC PWB 14A VIRGIN WITH 50% REGRIND
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006205 2 ■

Information Handling Services, 2000

82525 PLASTIC PWB 14B 100% REGRIND
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82526 PLASTIC PWB 14B VIRGIN
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82527 PLASTIC PWB 14B VIRGIN WITH 20% REGRIND
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82528 PLASTIC PWB 14B VIRGIN WITH 50% REGRIND
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82529 PLASTIC PWB 21A
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82530 PLASTIC PWB 21A 100% REGRIND
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82531 PLASTIC PWB 21A VIRGIN
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82532 PLASTIC PWB 21A VIRGIN WITH 20% REGRIND
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82533 PLASTIC PWB 21A VIRGIN WITH 50% REGRIND
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82534 PLASTIC PWB 21B
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82536 PLASTIC PWB 21B VIRGIN
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82537 PLASTIC PWB 21B VIRGIN WITH 20% REGRIND
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82538 PLASTIC PWB 21B VIRGIN WITH 50% REGRIND
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

84987 PLASTIC Q1-5036
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006206 4 ■

Information Handling Services, 2000

69731 PLASTIC RCAS 0600
MANF: RICHMOND
....NO TEST DATA AVAILABLE....

69732 PLASTIC RCAS 1200
MANF: RICHMOND

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.70	.16	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

62468 PLASTIC RCAS 2400/ANTISTATIC 2 MIL THICK ROLLED INTO TUBULAR SHAPE GID: DUXXXX
MANF: RICHMOND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	012.3	0.002			06.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.75	.18	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

69730 PLASTIC RCAS 3600
MANF: RICHMOND
....NO TEST DATA AVAILABLE....

69733 PLASTIC RCAS 4200
MANF: RICHMOND
....NO TEST DATA AVAILABLE....

84642 PLASTIC RE2038/HD3404
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84643 PLASTIC RE2038/HD3475 UNFILLED
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84646 PLASTIC RE2038/HD3490
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84648 PLASTIC RE2039/HD0243
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84647 PLASTIC RE2039/HD242
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84640 PLASTIC RE2039/HD3404
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84651 PLASTIC RE2039/HD3410
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84653 PLASTIC RE2039/HD3469
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006207 6

84656 PLASTIC RE2039/HD3475 UNFILLED
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84661 PLASTIC RE2039/HD3561
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84663 PLASTIC RE2039/HD3615
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84665 PLASTIC RE2039/HD3719
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84667 PLASTIC RE2039/HD3840
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84657 PLASTIC RER2039/HD3490
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

82320 PLASTIC RESINOID 1312
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82321 PLASTIC RESINOID 1320
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82322 PLASTIC RESINOID 1321
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82323 PLASTIC RESINOID 1322
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82324 PLASTIC RESINOID 1323
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82325 PLASTIC RESINOID 1324
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82326 PLASTIC RESINOID 1325
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82327 PLASTIC RESINOID 1340
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006208 8 ■

Information Handling Services, 2000

82328 PLASTIC RESINOID 1360
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82329 PLASTIC RESINOID 1362
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82330 PLASTIC RESINOID 1370
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82331 PLASTIC RESINOID 1401
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82332 PLASTIC RESINOID 1402
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82333 PLASTIC RESINOID 2002-2
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82334 PLASTIC RESINOID 2002-4
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82335 PLASTIC RESINOID 2002-4P
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82336 PLASTIC RESINOID 2002C5
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82338 PLASTIC RESINOID 2016
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82339 PLASTIC RESINOID 2017
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82340 PLASTIC RESINOID 2018
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82341 PLASTIC RESINOID 7003S
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82342 PLASTIC RESINOID 7005
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

82343 PLASTIC RESINOID 7051
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82344 PLASTIC RESINOID 7051SS
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82345 PLASTIC RESINOID 7201
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

67777 PLASTIC RESINOL TYPE A
MANF: ALLIED RESINOUS PRODUCTS INC
....NO TEST DATA AVAILABLE....

67779 PLASTIC RESINOL TYPE D
MANF: ALLIED RESINOUS PRODUCTS INC
....NO TEST DATA AVAILABLE....

67778 PLASTIC RESINOL TYPE F
MANF: ALLIED RESINOUS PRODUCTS INC
....NO TEST DATA AVAILABLE....

69580 PLASTIC RESIOUR AR
MANF: HASBROUCK PLASTICS INC
....NO TEST DATA AVAILABLE....

69579 PLASTIC RESIOUR T
MANF: HASBROUCK PLASTICS INC
....NO TEST DATA AVAILABLE....

69577 PLASTIC RESTOUR P
MANF: HASBROUCK PLASTICS INC
....NO TEST DATA AVAILABLE....

69578 PLASTIC RESTOUR V
MANF: HASBROUCK PLASTICS INC
....NO TEST DATA AVAILABLE....

81457 PLASTIC REXENE PE147
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

81458 PLASTIC REXENE PP11520V
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

81459 PLASTIC REXENE PP14S2A
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

81460 PLASTIC REXENE PP31SA
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006210 6

Information Handling Services, 2000

80797 PLASTIC RILSAN AECNO TL
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80798 PLASTIC RILSAN AESNO P10 TL
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80799 PLASTIC RILSAN AESNO P20 TL
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80800 PLASTIC RILSAN AESNO P40 TL
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80801 PLASTIC RILSAN AESNO TL
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80802 PLASTIC RILSAN AMNO
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80803 PLASTIC RILSAN AMNY
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80804 PLASTIC RILSAN AUM 30
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80805 PLASTIC RILSAN AZM 30
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80806 PLASTIC RILSAN BECNO W3TL
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80807 PLASTIC RILSAN BESNO
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80808 PLASTIC RILSAN BESNO F15TL
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80810 PLASTIC RILSAN BMN G8
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80811 PLASTIC RILSAN BMNO
MANF: ATOCHEM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.93	.03	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

MSFC-HDBK-527 REV F 9999942 0006211 8

Information Handling Services, 2000

80812 PLASTIC RILSAN BMNY
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80813 PLASTIC RILSAN BZM23 BLK TL
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80814 PLASTIC RILSAN BZM23G9
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80815 PLASTIC RILSAN BZM43 BLK
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80816 PLASTIC RILSAN BZM43G9
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80817 PLASTIC RILSAN BZMO30
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80818 PLASTIC RILSAN NYLON 12 MOLDING GRADE AZM23G9
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80819 PLASTIC RILSAN NYLON 12 MOLDING GRADE AZM43G9
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80809 PLASTIC RILSAN P40TL
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

80821 PLASTIC RILSAN SR100
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

85001 PLASTIC RIMPLAST NYLON 12
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

85004 PLASTIC RIMPLAST NYLON 6/6
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

85006 PLASTIC RIMPLAST PTA 1201
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

85008 PLASTIC RIMPLAST PTA 1202
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006212 T ■

Information Handling Services, 2000

DATE: 12/23/88
NON-METALS BY DESIGNATION

85010 PLASTIC RIMPLAST PTA 6601
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

85013 PLASTIC RIMPLAST PTA 6602
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

85014 PLASTIC RIMPLAST PTA 6631
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

84944 PLASTIC RIMPLAST PTEE 601
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

84947 PLASTIC RIMPLAST PTEE 602
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

84950 PLASTIC RIMPLAST PTSEBS 1204
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

84953 PLASTIC RIMPLAST PTSEBS 2204
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

84957 PLASTIC RIMPLAST PTUA 102
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

84961 PLASTIC RIMPLAST PTUA 103
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

84964 PLASTIC RIMPLAST PTUE 101
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

84967 PLASTIC RIMPLAST PTUE 102
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

84969 PLASTIC RIMPLAST PTUE 202
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

84972 PLASTIC RIMPLAST PTUE 203
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

84976 PLASTIC RIMPLAST PTUE 205
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006213 1

Information Handling Services, 2000

84986 PLASTIC RIMPLAST PTUE 302
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

84989 PLASTIC RIMPLAST PTUE 332
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

84992 PLASTIC RIMPLAST R1000
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

85012 PLASTIC RIMPLAST R5000
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

85015 PLASTIC RIMPLAST RF-1006
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

85017 PLASTIC RIMPLAST RF-5006
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

85018 PLASTIC RIMPLAST RL-4610
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

85020 PLASTIC RIMPLAST RL-4620
MANF: PETRARCH SYSTEMS INC
....NO TEST DATA AVAILABLE....

85504 PLASTIC ROD METHACRYLATE
MANF: TFE INDUSTRIES
....NO TEST DATA AVAILABLE....

SPEC: LP-391 T2

80599 PLASTIC ROSITE 3250A
MANF: ALLEN-BRADLEY CO ROSTONE DIV
....NO TEST DATA AVAILABLE....

80600 PLASTIC ROSITE 3250C
MANF: ALLEN-BRADLEY CO ROSTONE DIV
....NO TEST DATA AVAILABLE....

80601 PLASTIC ROSITE 3550A
MANF: ALLEN-BRADLEY CO ROSTONE DIV
....NO TEST DATA AVAILABLE....

80602 PLASTIC ROSITE 3550C
MANF: ALLEN-BRADLEY CO ROSTONE DIV
....NO TEST DATA AVAILABLE....

80603 PLASTIC ROSITE 3550FM
MANF: ALLEN-BRADLEY CO ROSTONE DIV
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006214 3

Information Handling Services, 2000

82510 PLASTIC ROTOFLAME RF1001
MANF: ROTOTRON
....NO TEST DATA AVAILABLE....

82511 PLASTIC ROTOTHENE R2010
MANF: ROTOTRON
....NO TEST DATA AVAILABLE....

82512 PLASTIC ROTOTHENE R8107U
MANF: ROTOTRON
....NO TEST DATA AVAILABLE....

82514 PLASTIC ROTOTHENE R8307U
MANF: ROTOTRON
....NO TEST DATA AVAILABLE....

82513 PLASTIC ROTOTHENE R835U
MANF: ROTOTRON
....NO TEST DATA AVAILABLE....

82515 PLASTIC ROTOTHENE R8405
MANF: ROTOTRON
....NO TEST DATA AVAILABLE....

82516 PLASTIC ROTOTHON XP1
MANF: ROTOTRON
....NO TEST DATA AVAILABLE....

20046 PLASTIC ROYALITE 54 GID: DUAIXX
MANF: UNIROYAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.032			11.20	T SMALL
I	1	023.8	014.5	0.038			11.90	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00070.52	

20011 PLASTIC ROYALITE 57 GID: DUAIXX
MANF: UNIROYAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.125			01.20	NONE
B	1	023.8	014.5	0.061		00.10	07.70	NONE
A	1	100.0	014.7	0.127			00.20	NONE
A	1	100.0	014.7	0.058			01.60	SMALL

FSC

RT	FLUID NAME
C	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

84078 PLASTIC RP-1220
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84079 PLASTIC RP-1225
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84080 PLASTIC RP-1710
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006215 5

84081 PLASTIC RP-1720
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84082 PLASTIC RP-1774
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84085 PLASTIC RP-3209-1
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84086 PLASTIC RP-3209-2
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84087 PLASTIC RP-3215-1
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84089 PLASTIC RP-3215-2
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84091 PLASTIC RP-3215-3
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84112 PLASTIC RP-3253
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84111 PLASTIC RP-3261
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84116 PLASTIC RP-3262
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84118 PLASTIC RP-3266 45/55
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84120 PLASTIC RP-3266 5-/45
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84122 PLASTIC RP-3266 50/50
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84124 PLASTIC RP-3269
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006216 7 ■

Information Handling Services, 2000

84126 PLASTIC RP-3269-1
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84128 PLASTIC RP-3270 CASTING
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84130 PLASTIC RP-3270 LAMINATING
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84138 PLASTIC RP-4003
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84132 PLASTIC RP-4005/1500H
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84491 PLASTIC RP-4036/RP-1500H
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84494 PLASTIC RP-4104R/1500H
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84332 PLASTIC RP1118
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84333 PLASTIC RP1125
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84334 PLASTIC RP1126
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84335 PLASTIC RP1129
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84336 PLASTIC RP1700
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84083 PLASTIC RP306
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84337 PLASTIC RP3260
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

84338 PLASTIC RP4018R/RP1520H
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84339 PLASTIC RP4026/RP1501
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

82539 PLASTIC RTP 1000FRA
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82540 PLASTIC RTP 1002FRA
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82541 PLASTIC RTP 1005FR
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82542 PLASTIC RTP 1005FRA
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82543 PLASTIC RTP 101FR
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82544 PLASTIC RTP 103
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82545 PLASTIC RTP 103CC
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82546 PLASTIC RTP 103SP
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82547 PLASTIC RTP 105CC FR
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82548 PLASTIC RTP 1103
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82549 PLASTIC RTP 1105FR
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82555 PLASTIC RTP 1205
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006218 0 ■

Information Handling Services, 2000

82552 PLASTIC RTP 128
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82554 PLASTIC RTP 1303
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82556 PLASTIC RTP 1378
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82557 PLASTIC RTP 1383
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82558 PLASTIC RTP 1383 TFE 15
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82559 PLASTIC RTP 1385
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82560 PLASTIC RTP 1385 TFE 15
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82561 PLASTIC RTP 1385HEC
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82562 PLASTIC RTP 1387
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82563 PLASTIC RTP 1387HEC
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82564 PLASTIC RTP 1403
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82565 PLASTIC RTP 1405
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82566 PLASTIC RTP 141
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82567 PLASTIC RTP 150
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006219 2

Information Handling Services, 2000

82570 PLASTIC RTP 152
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82571 PLASTIC RTP 199 X 22898
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82572 PLASTIC RTP 199 X 23835
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82577 PLASTIC RTP 199 X 28016
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82578 PLASTIC RTP 199 X 28016 HI1
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82579 PLASTIC RTP 199 X 28016 HI2
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82574 PLASTIC RTP 199 X 28017C
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82580 PLASTIC RTP 199 X 28559
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82581 PLASTIC RTP 199 X 50148C
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82582 PLASTIC RTP 199 X 50466A
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82583 PLASTIC RTP 199 X 50466B
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82575 PLASTIC RTP 199 X 50485
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82576 PLASTIC RTP 199 X 50486A
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82584 PLASTIC RTP 199 X 50486B
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006220 9 ■

Information Handling Services, 2000

82585 PLASTIC RTP 199 X 50487B
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82586 PLASTIC RTP 199 X 50487B HI1
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82587 PLASTIC RTP 199 X 50487B HI2
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82588 PLASTIC RTP 199 X 50504
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82589 PLASTIC RTP 199 X 50505
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82573 PLASTIC RTP 199-38016
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82592 PLASTIC RTP 200 TFE 20
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82590 PLASTIC RTP 200FR
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82593 PLASTIC RTP 200H FR
MANF: RE CORP
....NO TEST DATA AVAILABLE....

82591 PLASTIC RTP 200MS
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82594 PLASTIC RTP 202FR
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82595 PLASTIC RTP 203
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82599 PLASTIC RTP 203 TFE 20
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82596 PLASTIC RTP 203A
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006221 0 ■

82597 PLASTIC RTP 203D
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82598 PLASTIC RTP 203H
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82600 PLASTIC RTP 204FR
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82603 PLASTIC RTP 205D FR
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82601 PLASTIC RTP 205FR
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82602 PLASTIC RTP 205MS
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82604 PLASTIC RTP 2105
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82605 PLASTIC RTP 2205
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82606 PLASTIC RTP 225
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82607 PLASTIC RTP 283
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82608 PLASTIC RTP 283 TFE 10
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82609 PLASTIC RTP 285
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82611 PLASTIC RTP 285 TFE 15
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82612 PLASTIC RTP 285HEC
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006222 2 ■

Information Handling Services, 2000

82610 PLASTIC RTP 285P
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82613 PLASTIC RTP 287
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82614 PLASTIC RTP 287HEC
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82615 PLASTIC RTP 287P
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82616 PLASTIC RTP 299A 27567
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82617 PLASTIC RTP 301FR
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82618 PLASTIC RTP 303
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82620 PLASTIC RTP 303 TFE 10
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82619 PLASTIC RTP 303FR
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82622 PLASTIC RTP 305 TFE 15
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82621 PLASTIC RTP 305FR
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82623 PLASTIC RTP 307FR
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82624 PLASTIC RTP 383
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82626 PLASTIC RTP 383 TFE 20
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006223 4

82625 PLASTIC RTP 383FR
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82627 PLASTIC RTP 385
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82628 PLASTIC RTP 385 TFE 15
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82629 PLASTIC RTP 385HEC
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82630 PLASTIC RTP 387
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82631 PLASTIC RTP 387HEC
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82632 PLASTIC RTP 403
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82633 PLASTIC RTP 503
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82634 PLASTIC RTP 603
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82636 PLASTIC RTP 685
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82637 PLASTIC RTP 685HEC
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82638 PLASTIC RTP 687
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82639 PLASTIC RTP 687HEC
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82640 PLASTIC RTP 703
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006224 6 ■

Information Handling Services, 2000

82635 PLASTIC RTP 783
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82641 PLASTIC RTP 799 X 50492
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82642 PLASTIC RTP 800 TFE 20
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82643 PLASTIC RTP 803
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82644 PLASTIC RTP 805 TFE 15
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82645 PLASTIC RTP 885
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82646 PLASTIC RTP 903
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

82647 PLASTIC RTP 905
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

83113 PLASTIC RTV SWS04478
MANF: STAUFFER CHEMICAL
....NO TEST DATA AVAILABLE....

83114 PLASTIC RTV SWS843
MANF: STAUFFER CHEMICAL
....NO TEST DATA AVAILABLE....

68553 PLASTIC RULON 123, PTFE
MANF: DIXON INDUSTRIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.00	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05300 PLASTIC RULON A TFE/GLASS GID: DKCNIA
MANF: DIXON INDUSTRIES
PORT PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.124			00.10	NONE

FSC

RT	FLUID NAME
A	HYZE
A	MMH
C	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	170	0.063	0	20
B	PNEU	1000		70	0.063	0	20
X	PNEU	1050		250	0.060	4	188
B	MECH	1050	72	250	0.061	1	180
B	PNEU	1500		70	0.124	0	20
B	MECH	1500	72	70	0.124	0	100

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006225 8

05300 PLASTIC RULON A TFE/GLASS (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1500	72	70	0.124	0	20
Z	MECH	2500	29	75	0.150	0	40
B	MECH	600	72	-297	0.031	0	80
C	MECH	8500	29	75	0.150	0	120

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.11	.01	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.56	

68568 PLASTIC RULON E, PTFE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68569 PLASTIC RULON G-65, PTFE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68580 PLASTIC RULON II
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

05495 PLASTIC RULON J TFE/GLASS GID: AHCPXX
MANF: DIXON INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.014			01.30	NONE

FSC

RT	FLUID NAME
A	HYZE
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	1500	60	70	0.061	00	20
X	PNEU	1500		70	0.061	2	16

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.11	.01	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00180.77	

68552 PLASTIC RULON J, PTFE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68551 PLASTIC RULON LD, PTFE
MANF: DIXON INDUSTRIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.00	.00	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

68567 PLASTIC RULON LOP-A, PTFE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68554 PLASTIC RULON W-2, PTFE
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

85168 PLASTIC RYNITE 430
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68663 PLASTIC RYNITE 530
MANF: DUPONT
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006226 T

62448 PLASTIC RYNITE 545 GID: DKXXXX
MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.8E-6	.58	.02	.06	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

68664 PLASTIC RYNITE 555
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68662 PLASTIC RYNITE 935
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85170 PLASTIC RYNITE 940
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85172 PLASTIC RYNITE 940FB
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85174 PLASTIC RYNITE FR543
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85176 PLASTIC RYNITE FR945
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85173 PLASTIC RYNITE RF530
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85178 PLASTIC RYNITE SST35
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68590 PLASTIC RYTON 15% TFE 30% CF
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE ...

61781 PLASTIC RYTON PPS GID: DKCHXX
MANF: PHILLIPS CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
C	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85175 PLASTIC RYTON R-10 5002C
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85180 PLASTIC RYTON R-10 5004A
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006227 1

85188 PLASTIC RYTON R-10 7006A
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

85204 PLASTIC RYTON R-3
MANF: PHILLIPS CHEMICAL
....NO TEST DATA AVAILABLE....

68579 PLASTIC RYTON R-8
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

81661 PLASTIC S660
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81662 PLASTIC S680
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81663 PLASTIC S690
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81664 PLASTIC S695
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81665 PLASTIC S706
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81666 PLASTIC S706M
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

84796 PLASTIC SAN 125
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

68482 PLASTIC SF-20CF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68484 PLASTIC SF-20CF/000
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68457 PLASTIC SF-30CF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68459 PLASTIC SF-30CF/15T
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006228 3 ■

Information Handling Services, 2000

68481 PLASTIC SF-30GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68458 PLASTIC SF-30GF/15T
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68483 PLASTIC SF-40CF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

68456 PLASTIC SF-40GF
MANF: COMPOUNDING TECHNOLOGY (CTI)
....NO TEST DATA AVAILABLE....

20520 PLASTIC SHEET ABS BLACK GID: DUAIXX
MANF: KAUFMAN GLASS CO SPEC: ST91P653-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
I	1	025.9	014.3	0.191		00.01	05.10	T	NONE
X	2	025.9	014.3	0.095			01.90		MOD
X	1	025.9	014.3	0.095		00.13	12.00	T	MOD
C	2	025.9	014.3	0.124			01.50		NONE
C	1	025.9	014.3	0.124		00.12	12.00	T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.9E-7	.43	.02		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.07	

61753 PLASTIC SHEET SARNEX #15 GID: DUCFAE
MANF: DOW CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
X	2	023.8	014.5	0.003		00.10	12.00	T	NONE
X	1	023.8	014.5	0.003		01.80	12.00	T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.8E-6	.32	.06		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00006.09	

81667 PLASTIC SI9002
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

81668 PLASTIC SI9041
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

69277 PLASTIC SMC
MANF: FILLITE U S A INC
....NO TEST DATA AVAILABLE....

69748 PLASTIC STAINLESS STEEL PUTTY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

82896 PLASTIC STAT-KON AC-1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006229 5

83080 PLASTIC STAT-KON AC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82900 PLASTIC STAT-KON AS-F
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82903 PLASTIC STAT-KON AS-FE
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82906 PLASTIC STAT-KON BLM
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82909 PLASTIC STAT-KON D
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82911 PLASTIC STAT-KON D-FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82913 PLASTIC STAT-KON DC-1003-FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82917 PLASTIC STAT-KON DC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82927 PLASTIC STAT-KON DCF-1006 15C/15G
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82931 PLASTIC STAT-KON DCL-4033
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82933 PLASTIC STAT-KON DF-15
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82935 PLASTIC STAT-KON DF-FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82938 PLASTIC STAT-KON EC-1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82942 PLASTIC STAT-KON EC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006230 1 ■

Information Handling Services, 2000

82945 PLASTIC STAT-KON FE
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82948 PLASTIC STAT-KON FP-CC-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82950 PLASTIC STAT-KON FP-E
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82954 PLASTIC STAT-KON FP-EC-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82956 PLASTIC STAT-KON FP-P
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82960 PLASTIC STAT-KON FP-PC-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82963 PLASTIC STAT-KON FP-VC-1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82966 PLASTIC STAT-KON GC-1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82969 PLASTIC STAT-KON GC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82972 PLASTIC STAT-KON H
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82974 PLASTIC STAT-KON IC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82976 PLASTIC STAT-KON JC-1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82979 PLASTIC STAT-KON JC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82982 PLASTIC STAT-KON KC-1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

82985 PLASTIC STAT-KON KCL-4022
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82989 PLASTIC STAT-KON LC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

82997 PLASTIC STAT-KON LCL-4033
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83001 PLASTIC STAT-KON M1 HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83004 PLASTIC STAT-KON M2
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83007 PLASTIC STAT-KON ME
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83010 PLASTIC STAT-KON MF-15
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83012 PLASTIC STAT-KON MM3340
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83014 PLASTIC STAT-KON OC-1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83018 PLASTIC STAT-KON OC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83021 PLASTIC STAT-KON OCL-4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83028 PLASTIC STAT-KON PC-1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83029 PLASTIC STAT-KON PC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83034 PLASTIC STAT-KON PDX-84368 PC
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006232 5

Information Handling Services, 2000

NON-METALS BY DESIGNATION

83037 PLASTIC STAT-KON QC-1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83039 PLASTIC STAT-KON QC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83041 PLASTIC STAT-KON R
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83042 PLASTIC STAT-KON RC-1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83044 PLASTIC STAT-KON RC-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83046 PLASTIC STAT-KON RC-1004-FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83048 PLASTIC STAT-KON RC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83049 PLASTIC STAT-KON RC-1006-HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83051 PLASTIC STAT-KON RCF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83054 PLASTIC STAT-KON RCL-4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83056 PLASTIC STAT-KON RCL-4042
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83059 PLASTIC STAT-KON RCL-4536
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83063 PLASTIC STAT-KON RF-15
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83066 PLASTIC STAT-KON T
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

83068 PLASTIC STAT-KON VC-1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83070 PLASTIC STAT-KON WC-1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83073 PLASTIC STAT-KON WC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83077 PLASTIC STAT-KON ZC-1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

69742 PLASTIC STEEL 5-MIN. PUTTY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

69741 PLASTIC STEEL LIQUID
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

84532 PLASTIC STYCAST 1267
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84461 PLASTIC STYCAST 1269A
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.18	.05	.00	16H-212F- 24H-302F-	No test data		

84462 PLASTIC STYCAST 1495
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84463 PLASTIC STYCAST 2057
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.73	.01	.00	24H-70F-	No test data		

84464 PLASTIC STYCAST 2058
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84465 PLASTIC STYCAST 2651-1
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84466 PLASTIC STYCAST 2651-40
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006234 9

84467 PLASTIC STYCAST 2651MM-1
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84468 PLASTIC STYCAST 2750FR-M
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84469 PLASTIC STYCAST 2760
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84470 PLASTIC STYCAST 2850MT
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.52	.02	.00	24H-70F-

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

84471 PLASTIC STYCAST 2851FT
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84472 PLASTIC STYCAST 2851KT
MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.29	.04	.00	2H-223F-

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

84473 PLASTIC STYCAST 2851MT
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84474 PLASTIC STYCAST 3020SC
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84475 PLASTIC STYCAST 3180M
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

81713 PLASTIC STYPOL 047-1000
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

81714 PLASTIC STYPOL 047-1050
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69362 PLASTIC STYPOL 40-0008
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69302 PLASTIC STYPOL 40-0042
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

69309 PLASTIC STYPOL 40-0048
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69307 PLASTIC STYPOL 40-0087
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69394 PLASTIC STYPOL 40-1021
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69310 PLASTIC STYPOL 40-1037
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69304 PLASTIC STYPOL 40-1103
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69311 PLASTIC STYPOL 40-1117
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69305 PLASTIC STYPOL 40-1124
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69312 PLASTIC STYPOL 40-1507
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69306 PLASTIC STYPOL 40-1602
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69313 PLASTIC STYPOL 40-1603
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69314 PLASTIC STYPOL 40-2025
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69315 PLASTIC STYPOL 40-2026
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69308 PLASTIC STYPOL 40-2057
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69339 PLASTIC STYPOL 40-2072
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006236 2 ■

Information Handling Services, 2000

69317 PLASTIC STYPOL 40-2092
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69340 PLASTIC STYPOL 40-2304
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69318 PLASTIC STYPOL 40-2353
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69341 PLASTIC STYPOL 40-2364
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69319 PLASTIC STYPOL 40-2405
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69342 PLASTIC STYPOL 40-2448
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69320 PLASTIC STYPOL 40-2465
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69344 PLASTIC STYPOL 40-2580
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69343 PLASTIC STYPOL 40-2584
MANF: FREEMAN CHEMICAL CORP
.....NO TEST DATA AVAILABLE....

81715 PLASTIC STYPOL 40-2780
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69322 PLASTIC STYPOL 40-2782
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69321 PLASTIC STYPOL 40-27II
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69345 PLASTIC STYPOL 40-2974
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69323 PLASTIC STYPOL 40-2988
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006237 4

Information Handling Services, 2000

69346 PLASTIC STYPOL 40-2989
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69324 PLASTIC STYPOL 40-2990
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69347 PLASTIC STYPOL 40-3267
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69325 PLASTIC STYPOL 40-3303
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69348 PLASTIC STYPOL 40-3323
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69326 PLASTIC STYPOL 40-3904
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69349 PLASTIC STYPOL 40-3906
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69327 PLASTIC STYPOL 40-3909
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69350 PLASTIC STYPOL 40-3925
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

81716 PLASTIC STYPOL 40-3925 43% GLASS
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

81717 PLASTIC STYPOL 40-3925 50% GLASS
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69328 PLASTIC STYPOL 40-3929
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69351 PLASTIC STYPOL 40-3939
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69329 PLASTIC STYPOL 40-3941
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006238 6 ■

Information Handling Services, 2000

69352 PLASTIC STYPOL 40-3950
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69330 PLASTIC STYPOL 40-4901
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69353 PLASTIC STYPOL 40-4902
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69331 PLASTIC STYPOL 40-4920
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69354 PLASTIC STYPOL 40-5013
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69332 PLASTIC STYPOL 40-6519
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69355 PLASTIC STYPOL 40-7001
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69333 PLASTIC STYPOL 40-7052
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69356 PLASTIC STYPOL 40-7114
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

81718 PLASTIC STYPOL 40-7116
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69334 PLASTIC STYPOL 40-7119
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69357 PLASTIC STYPOL 40-7131
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69335 PLASTIC STYPOL 40-7134
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69358 PLASTIC STYPOL 40-7193
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006239 8 ■

Information Handling Services, 2000

69336 PLASTIC STYPOL 40-7263
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69359 PLASTIC STYPOL 40-8003
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69337 PLASTIC STYPOL 40-8408
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69360 PLASTIC STYPOL 40-9303
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69338 PLASTIC STYPOL 40-9311
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69361 PLASTIC STYPOL 40-9518
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69303 PLASTIC STYPOL 40-I029
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

81719 PLASTIC STYPOL 42-2640
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

81720 PLASTIC STYPOL 42-2675
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69381 PLASTIC STYPOL 70-0001
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69388 PLASTIC STYPOL 70-0004
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69382 PLASTIC STYPOL 72-5038
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69383 PLASTIC STYPOL 80-1126
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69384 PLASTIC STYPOL 80-3297
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006240 4

Information Handling Services, 2000

69389 PLASTIC STYPOL 80-II20
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69390 PLASTIC STYPOL 80-II27
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69391 PLASTIC STYPOL 83-2000
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69385 PLASTIC STYPOL 83-2030
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69392 PLASTIC STYPOL 83-2035
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69386 PLASTIC STYPOL 83-2105
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69393 PLASTIC STYPOL 83-2139
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

69387 PLASTIC STYPOL 83-2140
MANF: FREEMAN CHEMICAL CORP
....NO TEST DATA AVAILABLE....

83526 PLASTIC STYRAFIL G-30/20
MANF: WILSON FIBERFIL

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.27	.02	.00		No test data		

83527 PLASTIC STYRAFIL G-30/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE. ..

83528 PLASTIC STYRAFIL G-35/35
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83529 PLASTIC STYRAFIL J-30/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83530 PLASTIC STYRAFIL J-30/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83531 PLASTIC STYRAFIL J-39/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006241 6

Information Handling Services, 2000

83533 PLASTIC STYRAFIL J-39/10/E
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83535 PLASTIC STYRAFIL J-39/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83536 PLASTIC STYRAFIL J-39/20/D
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83538 PLASTIC STYRAFIL J-39/20/E
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83540 PLASTIC STYRAFIL J-39/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83541 PLASTIC STYRAFIL J-39/30/E
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83544 PLASTIC STYRAFIL J-39/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83547 PLASTIC STYRAFIL J-39/40/E
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

80887 PLASTIC STYRODUR 3000
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80888 PLASTIC STYRODUR 4000
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80889 PLASTIC STYRODUR 5000
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

84810 PLASTIC STYRON 656D
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84811 PLASTIC STYRON 666D
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84812 PLASTIC STYRON 678D
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006242 8

Information Handling Services, 2000

84813 PLASTIC STYRON 678U
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84814 PLASTIC STYRON 685
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84816 PLASTIC STYRON 685D
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84818 PLASTIC STYRON 697
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

67780 PLASTIC STYRONOL
MANF: ALLIED RESINOUS PRODUCTS INC
....NO TEST DATA AVAILABLE....

83549 PLASTIC SULFIL G-1500/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83551 PLASTIC SULFIL G-1500/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83553 PLASTIC SULFIL J-1100/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83558 PLASTIC SULFIL J-1100/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83561 PLASTIC SULFIL J-1100/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83563 PLASTIC SULFIL J-1105/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83565 PLASTIC SULFIL J-1300/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83567 PLASTIC SULFIL J-1300/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83569 PLASTIC SULFIL J-1300/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006243 T

Information Handling Services, 2000

83571 PLASTIC SULFIL J-1300/30/TF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83572 PLASTIC SULFIL J-1300/40
MANF: WILSON FIBERFIL

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	1.28	2.13	.00	.01H-399F-	No test data		

83574 PLASTIC SULFIL J-1500/10
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83576 PLASTIC SULFIL J-1500/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83579 PLASTIC SULFIL J-1500/20/TF/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83580 PLASTIC SULFIL J-1500/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83582 PLASTIC SULFIL J-1500/40
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83584 PLASTIC SULFIL J-1505/20
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

69574 PLASTIC SUPER FLOW 390
MANF: HAMMOND PLASTICS
....NO TEST DATA AVAILABLE....

69573 PLASTIC SUPER FLOW 400
MANF: HAMMOND PLASTICS
....NO TEST DATA AVAILABLE....

69575 PLASTIC SUPERDENSE 700
MANF: HAMMOND PLASTICS
....NO TEST DATA AVAILABLE....

69576 PLASTIC SUPERDENSE 710
MANF: HAMMOND PLASTICS
....NO TEST DATA AVAILABLE....

69572 PLASTIC SUPERFLEX 405
MANF: HAMMOND PLASTICS
....NO TEST DATA AVAILABLE....

69570 PLASTIC SUPERFLEX 425
MANF: HAMMOND PLASTICS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006244 1

Information Handling Services, 2000

69571 PLASTIC SUPERFLEX 432
MANF: HAMMOND PLASTICS
....NO TEST DATA AVAILABLE....

69569 PLASTIC SUPERFLEX 505
MANF: HAMMOND PLASTICS
....NO TEST DATA AVAILABLE....

69568 PLASTIC SUPERFLEX 550
MANF: HAMMOND PLASTICS
....NO TEST DATA AVAILABLE....

69567 PLASTIC SUPERFLEX FR-1
MANF: HAMMOND PLASTICS
....NO TEST DATA AVAILABLE....

80477 PLASTIC SUPEROHM 3728
MANF: A SCHULMAN INC
....NO TEST DATA AVAILABLE....

85181 PLASTIC SURLYN 8020
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85183 PLASTIC SURLYN 8528
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85185 PLASTIC SURLYN 8550
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85186 PLASTIC SURLYN 8660
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85189 PLASTIC SURLYN 8920
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85191 PLASTIC SURLYN 8940
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85193 PLASTIC SURLYN 9020
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85195 PLASTIC SURLYN 9450
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85197 PLASTIC SURLYN 9520
MANF: DUPONT
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006245 3

Information Handling Services, 2000

85198 PLASTIC SURLYN 9650
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85199 PLASTIC SURLYN 9721
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85200 PLASTIC SURLYN 9730
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85201 PLASTIC SURLYN 9910
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85202 PLASTIC SURLYN 9950
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85203 PLASTIC SURLYN 9970
MANF: DUPONT
....NO TEST DATA AVAILABLE....

69757 PLASTIC TANKITE II
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

84496 PLASTIC TDT-177-15
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

84499 PLASTIC TDT-177-62
MANF: CIBA-GEIGY
....NO TEST DATA AVAILABLE....

82347 PLASTIC TECHNYL A20
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82348 PLASTIC TECHNYL A20 V25
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82349 PLASTIC TECHNYL A216
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82350 PLASTIC TECHNYL A216 V10
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82351 PLASTIC TECHNYL A216 V15
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006246 5

Information Handling Services, 2000

DATE: 12/23/88
NON-METALS BY DESIGNATION

82352 PLASTIC TECHNYL A216 V20
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82353 PLASTIC TECHNYL A216 V25
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82354 PLASTIC TECHNYL A216 V30
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82355 PLASTIC TECHNYL A216 V35
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82356 PLASTIC TECHNYL A216 V40
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82357 PLASTIC TECHNYL A216 V50
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82358 PLASTIC TECHNYL A217
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82359 PLASTIC TECHNYL A218
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82360 PLASTIC TECHNYL A218 V20
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82361 PLASTIC TECHNYL A218 V25
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82362 PLASTIC TECHNYL A218 V30
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82363 PLASTIC TECHNYL A218 V40
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82364 PLASTIC TECHNYL A221
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82365 PLASTIC TECHNYL A222
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006247 7

Information Handling Services, 2000

82366 PLASTIC TECHNYL A228 MT40
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82367 PLASTIC TECHNYL A248 MT30
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82368 PLASTIC TECHNYL A319
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82369 PLASTIC TECHNYL B216
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82370 PLASTIC TECHNYL B216 V20
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82482 PLASTIC TECHNYL B216 V30
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82483 PLASTIC TECHNYL B216 V50
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82484 PLASTIC TECHNYL B217
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82485 PLASTIC TECHNYL B218
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82486 PLASTIC TECHNYL B218 MX30
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82487 PLASTIC TECHNYL B218 MX40
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82488 PLASTIC TECHNYL B230
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82489 PLASTIC TECHNYL C216
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82490 PLASTIC TECHNYL C216 V20
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006248 9 ■

Information Handling Services, 2000

82491 PLASTIC TECHNYL C216 V30
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82492 PLASTIC TECHNYL C316
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82493 PLASTIC TECHNYL D316
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

82494 PLASTIC TECHNYL D317
MANF: RHONE-POULENC
....NO TEST DATA AVAILABLE....

68666 PLASTIC TEDLAR
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68591 PLASTIC TEFLON 62 TFE
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68592 PLASTIC TEFLON 67 TFE
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68594 PLASTIC TEFLON 6C PTFE
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68595 PLASTIC TEFLON FEP 100
MANF: DUPONT

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.06	.06	.00		No test data		

68667 PLASTIC TEFLON FEP 120
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68602 PLASTIC TEFLON FEP 140
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68599 PLASTIC TEFLON TFE 160
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68600 PLASTIC TEFLON TFE 60
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68598 PLASTIC TEFLON TFE 64
MANF: DUPONT
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006249 0 ■

68601 PLASTIC TEFLON TFE 65
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68593 PLASTIC TEFLON TFE 66
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68604 PLASTIC TEFLON TFE 8
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68603 PLASTIC TEFLON TFE 8A
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68596 PLASTIC TEFLON TFE 8B
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68597 PLASTIC TEFLON TFE 9B
MANF: DUPONT
....NO TEST DATA AVAILABLE....

80542 PLASTIC TEFZEL 200
MANF: AFTON PLASTICS
....NO TEST DATA AVAILABLE....

80543 PLASTIC TEFZEL 210
MANF: AFTON PLASTICS
....NO TEST DATA AVAILABLE....

80544 PLASTIC TEFZEL 280
MANF: AFTON PLASTICS
....NO TEST DATA AVAILABLE....

68973 PLASTIC TENITE ACETATE FORMULA 007 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68972 PLASTIC TENITE ACETATE FORMULA 007 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68971 PLASTIC TENITE ACETATE FORMULA 007 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68970 PLASTIC TENITE ACETATE FORMULA 007 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68975 PLASTIC TENITE ACETATE FORMULA 007 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006250 7 ■

Information Handling Services, 2000

68974 PLASTIC TENITE ACETATE FORMULA 007 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68976 PLASTIC TENITE ACETATE FORMULA 007 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68977 PLASTIC TENITE ACETATE FORMULA 007 S
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68981 PLASTIC TENITE ACETATE FORMULA 036 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68980 PLASTIC TENITE ACETATE FORMULA 036 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68979 PLASTIC TENITE ACETATE FORMULA 036 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68978 PLASTIC TENITE ACETATE FORMULA 036 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68983 PLASTIC TENITE ACETATE FORMULA 036 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68982 PLASTIC TENITE ACETATE FORMULA 036 M4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68984 PLASTIC TENITE ACETATE FORMULA 036 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68988 PLASTIC TENITE ACETATE FORMULA 042 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68987 PLASTIC TENITE ACETATE FORMULA 042 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68986 PLASTIC TENITE ACETATE FORMULA 042 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68985 PLASTIC TENITE ACETATE FORMULA 042 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006251 9

68990 PLASTIC TENITE ACETATE FORMULA 042 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68989 PLASTIC TENITE ACETATE FORMULA 042 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68991 PLASTIC TENITE ACETATE FORMULA 042 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68992 PLASTIC TENITE ACETATE FORMULA 042 S2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68997 PLASTIC TENITE ACETATE FORMULA 043 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68996 PLASTIC TENITE ACETATE FORMULA 043 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68995 PLASTIC TENITE ACETATE FORMULA 043 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68994 PLASTIC TENITE ACETATE FORMULA 043 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68999 PLASTIC TENITE ACETATE FORMULA 043 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

68998 PLASTIC TENITE ACETATE FORMULA 043 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69000 PLASTIC TENITE ACETATE FORMULA 043 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69001 PLASTIC TENITE ACETATE FORMULA 043 S
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69002 PLASTIC TENITE ACETATE FORMULA 043 S2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69006 PLASTIC TENITE ACETATE FORMULA 054 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006252 0

Information Handling Services, 2000

69005 PLASTIC TENITE ACETATE FORMULA 054 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69004 PLASTIC TENITE ACETATE FORMULA 054 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69003 PLASTIC TENITE ACETATE FORMULA 054 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69008 PLASTIC TENITE ACETATE FORMULA 054 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69007 PLASTIC TENITE ACETATE FORMULA 054 M4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69009 PLASTIC TENITE ACETATE FORMULA 054 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69010 PLASTIC TENITE ACETATE FORMULA 054 S
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69014 PLASTIC TENITE ACETATE FORMULA 100 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69013 PLASTIC TENITE ACETATE FORMULA 100 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69012 PLASTIC TENITE ACETATE FORMULA 100 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69011 PLASTIC TENITE ACETATE FORMULA 100 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69016 PLASTIC TENITE ACETATE FORMULA 100 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69015 PLASTIC TENITE ACETATE FORMULA 100 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69017 PLASTIC TENITE ACETATE FORMULA 100 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006253 2

Information Handling Services, 2000

69021 PLASTIC TENITE ACETATE FORMULA 103 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69020 PLASTIC TENITE ACETATE FORMULA 103 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69019 PLASTIC TENITE ACETATE FORMULA 103 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69018 PLASTIC TENITE ACETATE FORMULA 103 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69023 PLASTIC TENITE ACETATE FORMULA 103 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69022 PLASTIC TENITE ACETATE FORMULA 103 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69024 PLASTIC TENITE ACETATE FORMULA 103 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69027 PLASTIC TENITE ACETATE FORMULA 104 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69026 PLASTIC TENITE ACETATE FORMULA 104 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69025 PLASTIC TENITE ACETATE FORMULA 104 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69031 PLASTIC TENITE BUTYRATE FORMULA 203 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69030 PLASTIC TENITE BUTYRATE FORMULA 203 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69029 PLASTIC TENITE BUTYRATE FORMULA 203 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69028 PLASTIC TENITE BUTYRATE FORMULA 203 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006254 4

Information Handling Services, 2000

69033 PLASTIC TENITE BUTYRATE FORMULA 203 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69032 PLASTIC TENITE BUTYRATE FORMULA 203 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69034 PLASTIC TENITE BUTYRATE FORMULA 203 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69035 PLASTIC TENITE BUTYRATE FORMULA 203 S
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69036 PLASTIC TENITE BUTYRATE FORMULA 203 S2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69040 PLASTIC TENITE BUTYRATE FORMULA 205 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69039 PLASTIC TENITE BUTYRATE FORMULA 205 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69038 PLASTIC TENITE BUTYRATE FORMULA 205 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69037 PLASTIC TENITE BUTYRATE FORMULA 205 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69042 PLASTIC TENITE BUTYRATE FORMULA 205 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69041 PLASTIC TENITE BUTYRATE FORMULA 205 M4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69043 PLASTIC TENITE BUTYRATE FORMULA 205 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69044 PLASTIC TENITE BUTYRATE FORMULA 205 S
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69045 PLASTIC TENITE BUTYRATE FORMULA 205 S2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006255 6

Information Handling Services, 2000

69049 PLASTIC TENITE BUTYRATE FORMULA 217 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69048 PLASTIC TENITE BUTYRATE FORMULA 217 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69047 PLASTIC TENITE BUTYRATE FORMULA 217 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69046 PLASTIC TENITE BUTYRATE FORMULA 217 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69056 PLASTIC TENITE BUTYRATE FORMULA 217 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69055 PLASTIC TENITE BUTYRATE FORMULA 217 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69057 PLASTIC TENITE BUTYRATE FORMULA 217 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69058 PLASTIC TENITE BUTYRATE FORMULA 217 S
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69059 PLASTIC TENITE BUTYRATE FORMULA 217 S2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69063 PLASTIC TENITE BUTYRATE FORMULA 236 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69062 PLASTIC TENITE BUTYRATE FORMULA 236 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69061 PLASTIC TENITE BUTYRATE FORMULA 236 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69060 PLASTIC TENITE BUTYRATE FORMULA 236 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69064 PLASTIC TENITE BUTYRATE FORMULA 236 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006256 8

Information Handling Services, 2000

69066 PLASTIC TENITE BUTYRATE FORMULA 236 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69067 PLASTIC TENITE BUTYRATE FORMULA 236 S
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69065 PLASTIC TENITE BUTYRATE FORMULA 236-M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69071 PLASTIC TENITE BUTYRATE FORMULA 264 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69070 PLASTIC TENITE BUTYRATE FORMULA 264 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69069 PLASTIC TENITE BUTYRATE FORMULA 264 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69068 PLASTIC TENITE BUTYRATE FORMULA 264 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69073 PLASTIC TENITE BUTYRATE FORMULA 264 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69072 PLASTIC TENITE BUTYRATE FORMULA 264 M4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69074 PLASTIC TENITE BUTYRATE FORMULA 264 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69075 PLASTIC TENITE BUTYRATE FORMULA 264 S
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69076 PLASTIC TENITE BUTYRATE FORMULA 264 S2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69080 PLASTIC TENITE BUTYRATE FORMULA 479 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69079 PLASTIC TENITE BUTYRATE FORMULA 479 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006257 T

Information Handling Services, 2000

69078 PLASTIC TENITE BUTYRATE FORMULA 479 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69077 PLASTIC TENITE BUTYRATE FORMULA 479 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69082 PLASTIC TENITE BUTYRATE FORMULA 479 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69081 PLASTIC TENITE BUTYRATE FORMULA 479 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69083 PLASTIC TENITE BUTYRATE FORMULA 479 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69087 PLASTIC TENITE BUTYRATE FORMULA 525 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69086 PLASTIC TENITE BUTYRATE FORMULA 525 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69085 PLASTIC TENITE BUTYRATE FORMULA 525 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69084 PLASTIC TENITE BUTYRATE FORMULA 525 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69089 PLASTIC TENITE BUTYRATE FORMULA 525 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69088 PLASTIC TENITE BUTYRATE FORMULA 525 M4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69090 PLASTIC TENITE BUTYRATE FORMULA 525 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69091 PLASTIC TENITE BUTYRATE FORMULA 525 S
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69092 PLASTIC TENITE BUTYRATE FORMULA 525 S2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006258 1

69096 PLASTIC TENITE BUTYRATE FORMULA 554 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69095 PLASTIC TENITE BUTYRATE FORMULA 554 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69094 PLASTIC TENITE BUTYRATE FORMULA 554 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69093 PLASTIC TENITE BUTYRATE FORMULA 554 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69098 PLASTIC TENITE BUTYRATE FORMULA 554 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69097 PLASTIC TENITE BUTYRATE FORMULA 554 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69099 PLASTIC TENITE BUTYRATE FORMULA 554 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69100 PLASTIC TENITE BUTYRATE FORMULA 554 S
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69101 PLASTIC TENITE BUTYRATE FORMULA 554 S2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

81436 PLASTIC TENITE BUTYRATE FORMULA H COMPRESSION
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

81437 PLASTIC TENITE BUTYRATE FORMULA H3 COMPRESSION
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

69221 PLASTIC TENITE POLYALLOMER 5020
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69220 PLASTIC TENITE POLYALLOMER 5021
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69223 PLASTIC TENITE POLYALLOMER 512V
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006259 3

Information Handling Services, 2000

69222 PLASTIC TENITE POLYALLOMER 5151
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69228 PLASTIC TENITE POLYETHYLENE 1390P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69242 PLASTIC TENITE POLYETHYLENE 1540F
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69225 PLASTIC TENITE POLYETHYLENE 1550
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69227 PLASTIC TENITE POLYETHYLENE 155W
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

81438 PLASTIC TENITE POLYETHYLENE 1572
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

69241 PLASTIC TENITE POLYETHYLENE 1800
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69233 PLASTIC TENITE POLYETHYLENE 1810
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69231 PLASTIC TENITE POLYETHYLENE 1811
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69235 PLASTIC TENITE POLYETHYLENE 183H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69234 PLASTIC TENITE POLYETHYLENE 183M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69236 PLASTIC TENITE POLYETHYLENE 1840
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69237 PLASTIC TENITE POLYETHYLENE 184L
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69238 PLASTIC TENITE POLYETHYLENE 184M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006260 T

Information Handling Services, 2000

69239 PLASTIC TENITE POLYETHYLENE 1870
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69240 PLASTIC TENITE POLYETHYLENE 18B0
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69230 PLASTIC TENITE POLYETHYLENE 1924P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69243 PLASTIC TENITE POLYETHYLENE 1925F
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69232 PLASTIC TENITE POLYETHYLENE 1930
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69224 PLASTIC TENITE POLYETHYLENE 800
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69229 PLASTIC TENITE POLYETHYLENE 808
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69226 PLASTIC TENITE POLYETHYLENE 811
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69244 PLASTIC TENITE POLYETHYLENE E6838-735
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69245 PLASTIC TENITE POLYETHYLENE E6838-768F
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69246 PLASTIC TENITE POLYETHYLENE E6838-781F
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69054 PLASTIC TENITE POLYETHYLENE E6838-793F
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69053 PLASTIC TENITE POLYETHYLENE E6838-807F
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69247 PLASTIC TENITE POLYETHYLENE E6838-849P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006261 1

Information Handling Services, 2000

69051 PLASTIC TENITE POLYETHYLENE E6838-868F
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69050 PLASTIC TENITE POLYETHYLENE E6838-913P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69052 PLASTIC TENITE POLYETHYLENE E6838-914P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

81439 PLASTIC TENITE POLYPROPYLENE
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

69183 PLASTIC TENITE POLYPROPYLENE 1550P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69184 PLASTIC TENITE POLYPROPYLENE 1924P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69195 PLASTIC TENITE POLYPROPYLENE 4220
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

81440 PLASTIC TENITE POLYPROPYLENE 422D
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

69197 PLASTIC TENITE POLYPROPYLENE 4230
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69196 PLASTIC TENITE POLYPROPYLENE 4231
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

81442 PLASTIC TENITE POLYPROPYLENE 4231E
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

69198 PLASTIC TENITE POLYPROPYLENE 4232
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

81443 PLASTIC TENITE POLYPROPYLENE 4232A
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

81444 PLASTIC TENITE POLYPROPYLENE 4240
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006262 3

Information Handling Services, 2000

69200 PLASTIC TENITE POLYPROPYLENE 4242
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69201 PLASTIC TENITE POLYPROPYLENE 4250
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

81446 PLASTIC TENITE POLYPROPYLENE 4250E
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

81445 PLASTIC TENITE POLYPROPYLENE 425A
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

69202 PLASTIC TENITE POLYPROPYLENE 4531
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69203 PLASTIC TENITE POLYPROPYLENE 4532
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69209 PLASTIC TENITE POLYPROPYLENE 4E11
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69193 PLASTIC TENITE POLYPROPYLENE 4E31
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69194 PLASTIC TENITE POLYPROPYLENE 4E3V
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69189 PLASTIC TENITE POLYPROPYLENE 4G7DP
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

81448 PLASTIC TENITE POLYPROPYLENE 4J31
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

81449 PLASTIC TENITE POLYPROPYLENE 4J32
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

69204 PLASTIC TENITE POLYPROPYLENE 4K31
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69205 PLASTIC TENITE POLYPROPYLENE 4K32
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006263 5

Information Handling Services, 2000

69206 PLASTIC TENITE POLYPROPYLENE 4L31
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69216 PLASTIC TENITE POLYPROPYLENE 4M40
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

81450 PLASTIC TENITE POLYPROPYLENE 4M40A
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

69207 PLASTIC TENITE POLYPROPYLENE 4P31
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69208 PLASTIC TENITE POLYPROPYLENE 4P32
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

81447 PLASTIC TENITE POLYPROPYLENE 5250G
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

69182 PLASTIC TENITE POLYPROPYLENE 808P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69188 PLASTIC TENITE POLYPROPYLENE E7-467P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69187 PLASTIC TENITE POLYPROPYLENE E8-849P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69185 PLASTIC TENITE POLYPROPYLENE E8-913P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69186 PLASTIC TENITE POLYPROPYLENE E8-914P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69199 PLASTIC TENITE POLYPROPYLENE H240
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69211 PLASTIC TENITE POLYPROPYLENE P7673-469P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69190 PLASTIC TENITE POLYPROPYLENE P7673-499P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006264 7

Information Handling Services, 2000

69191 PLASTIC TENITE POLYPROPYLENE P7673-607P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69212 PLASTIC TENITE POLYPROPYLENE P7673-648G
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69210 PLASTIC TENITE POLYPROPYLENE P7673-780A
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69213 PLASTIC TENITE POLYPROPYLENE P7673-940
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69215 PLASTIC TENITE POLYPROPYLENE P7673-984
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69192 PLASTIC TENITE POLYPROPYLENE P7673-996P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69214 PLASTIC TENITE POLYPROPYLENE R7673-930P
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

81451 PLASTIC TENITE PROPIONATE 338 FLOW H6 COMPRESSION
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

81452 PLASTIC TENITE PROPIONATE 338 FLOW H6 INJECTION
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

81453 PLASTIC TENITE PROPIONATE 350 FLOW H3 COMPRESSION
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

81454 PLASTIC TENITE PROPIONATE 350 FLOW H3 INJECTION
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

81455 PLASTIC TENITE PROPIONATE 358 FLOW H COMPRESSION
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

81456 PLASTIC TENITE PROPIONATE 358 FLOW H INJECTION
MANF: EASTMAN KODAK
....NO TEST DATA AVAILABLE....

69107 PLASTIC TENITE PROPIONATE FORMULA 306 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

69106 PLASTIC TENITE PROPIONATE FORMULA 306 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69105 PLASTIC TENITE PROPIONATE FORMULA 306 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69104 PLASTIC TENITE PROPIONATE FORMULA 306 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69103 PLASTIC TENITE PROPIONATE FORMULA 306 H5
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69102 PLASTIC TENITE PROPIONATE FORMULA 306 H6
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69108 PLASTIC TENITE PROPIONATE FORMULA 306 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69113 PLASTIC TENITE PROPIONATE FORMULA 309 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69112 PLASTIC TENITE PROPIONATE FORMULA 309 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69111 PLASTIC TENITE PROPIONATE FORMULA 309 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69110 PLASTIC TENITE PROPIONATE FORMULA 309 H5
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69109 PLASTIC TENITE PROPIONATE FORMULA 309 H6
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69118 PLASTIC TENITE PROPIONATE FORMULA 311 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69117 PLASTIC TENITE PROPIONATE FORMULA 311 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69116 PLASTIC TENITE PROPIONATE FORMULA 311 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006266 0 ■

Information Handling Services, 2000

69115 PLASTIC TENITE PROPIONATE FORMULA 311 H5
MANF: COLORITE PLASTICS CO
EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69114 PLASTIC TENITE PROPIONATE FORMULA 311 H6
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69123 PLASTIC TENITE PROPIONATE FORMULA 319 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69122 PLASTIC TENITE PROPIONATE FORMULA 319 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69121 PLASTIC TENITE PROPIONATE FORMULA 319 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69120 PLASTIC TENITE PROPIONATE FORMULA 319 H5
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69119 PLASTIC TENITE PROPIONATE FORMULA 319 H6
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69129 PLASTIC TENITE PROPIONATE FORMULA 325 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69128 PLASTIC TENITE PROPIONATE FORMULA 325 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69127 PLASTIC TENITE PROPIONATE FORMULA 325 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69126 PLASTIC TENITE PROPIONATE FORMULA 325 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69125 PLASTIC TENITE PROPIONATE FORMULA 325 H5
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69124 PLASTIC TENITE PROPIONATE FORMULA 325 H6
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69130 PLASTIC TENITE PROPIONATE FORMULA 325 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006267 2

Information Handling Services, 2000

69135 PLASTIC TENITE PROPIONATE FORMULA 326 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69134 PLASTIC TENITE PROPIONATE FORMULA 326 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69133 PLASTIC TENITE PROPIONATE FORMULA 326 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69132 PLASTIC TENITE PROPIONATE FORMULA 326 H5
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69131 PLASTIC TENITE PROPIONATE FORMULA 326 H6
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69141 PLASTIC TENITE PROPIONATE FORMULA 327 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69140 PLASTIC TENITE PROPIONATE FORMULA 327 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69139 PLASTIC TENITE PROPIONATE FORMULA 327 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69138 PLASTIC TENITE PROPIONATE FORMULA 327 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69137 PLASTIC TENITE PROPIONATE FORMULA 327 H5
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69136 PLASTIC TENITE PROPIONATE FORMULA 327 H6
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69142 PLASTIC TENITE PROPIONATE FORMULA 327 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69153 PLASTIC TENITE PROPIONATE FORMULA 333 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69152 PLASTIC TENITE PROPIONATE FORMULA 333 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006268 4

Information Handling Services, 2000

69151 PLASTIC TENITE PROPIONATE FORMULA 333 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69150 PLASTIC TENITE PROPIONATE FORMULA 333 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69149 PLASTIC TENITE PROPIONATE FORMULA 333 H5
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69148 PLASTIC TENITE PROPIONATE FORMULA 333 H6
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69155 PLASTIC TENITE PROPIONATE FORMULA 333 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69154 PLASTIC TENITE PROPIONATE FORMULA 333 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69161 PLASTIC TENITE PROPIONATE FORMULA 338 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69160 PLASTIC TENITE PROPIONATE FORMULA 338 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69159 PLASTIC TENITE PROPIONATE FORMULA 338 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69158 PLASTIC TENITE PROPIONATE FORMULA 338 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69157 PLASTIC TENITE PROPIONATE FORMULA 338 H5
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69156 PLASTIC TENITE PROPIONATE FORMULA 338 H6
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69162 PLASTIC TENITE PROPIONATE FORMULA 338 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69147 PLASTIC TENITE PROPIONATE FORMULA 350 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006269 6

Information Handling Services, 2000

69145 PLASTIC TENITE PROPIONATE FORMULA 350 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69144 PLASTIC TENITE PROPIONATE FORMULA 350 H5
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69143 PLASTIC TENITE PROPIONATE FORMULA 350 H6
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69168 PLASTIC TENITE PROPIONATE FORMULA 353 H
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69167 PLASTIC TENITE PROPIONATE FORMULA 353 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69166 PLASTIC TENITE PROPIONATE FORMULA 353 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69165 PLASTIC TENITE PROPIONATE FORMULA 353 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69164 PLASTIC TENITE PROPIONATE FORMULA 353 H5
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69163 PLASTIC TENITE PROPIONATE FORMULA 353 H6
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69170 PLASTIC TENITE PROPIONATE FORMULA 353 M
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69169 PLASTIC TENITE PROPIONATE FORMULA 353 MH
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69171 PLASTIC TENITE PROPIONATE FORMULA 353 MS
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69172 PLASTIC TENITE PROPIONATE FORMULA 353 S
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69173 PLASTIC TENITE PROPIONATE FORMULA 353 S2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006270 2

Information Handling Services, 2000

69175 PLASTIC TENITE PROPIONATE FORMULA 354 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69174 PLASTIC TENITE PROPIONATE FORMULA 354 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69180 PLASTIC TENITE PROPIONATE FORMULA 358 H2
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69179 PLASTIC TENITE PROPIONATE FORMULA 358 H3
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69178 PLASTIC TENITE PROPIONATE FORMULA 358 H4
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69177 PLASTIC TENITE PROPIONATE FORMULA 358 H5
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

69176 PLASTIC TENITE PROPIONATE FORMULA 358 H6
MANF: EASTMAN CHEMICAL PRODUCTS INC
....NO TEST DATA AVAILABLE....

80890 PLASTIC TERLURAN 828P
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80891 PLASTIC TERLURAN 848S
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80892 PLASTIC TERLURAN 857M
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80893 PLASTIC TERLURAN 867M
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80894 PLASTIC TERLURAN 877T/TE
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80895 PLASTIC TERLURAN 886T
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80896 PLASTIC TERLURAN 957SE
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006271 4

80897 PLASTIC TERLURAN 967K
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80898 PLASTIC TERLURAN 978T
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80899 PLASTIC TERLURAN 997VE
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80900 PLASTIC TERLURAN KR2543
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80901 PLASTIC TERLURAN KR2802/1
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80902 PLASTIC TERLURAN KR2882
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

83585 PLASTIC TETRAFIL J-1800/30
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83587 PLASTIC TETRAFIL J-1800/30/VO
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83589 PLASTIC TETRAFIL J-1800/45
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83590 PLASTIC TETRAFIL J-1800/55
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83593 PLASTIC TETRAFIL J-1850/15
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83595 PLASTIC TETRAFIL J-1850/30/VO
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83596 PLASTIC TETRAFIL J1875/30/VO
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

83219 PLASTIC TETRAFLUOR TF619
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006272 6

Information Handling Services, 2000

83220 PLASTIC TETRAFLUOR TFC021
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83221 PLASTIC TETRAFLUOR TFC025
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83222 PLASTIC TETRAFLUOR TFC030
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83223 PLASTIC TETRAFLUOR TFC031
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83224 PLASTIC TETRAFLUOR TFC033
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83225 PLASTIC TETRAFLUOR TFC045
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83226 PLASTIC TETRAFLUOR TFC082
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83227 PLASTIC TETRAFLUOR TFC086
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83228 PLASTIC TETRAFLUOR TFC108
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83229 PLASTIC TETRAFLUOR TFC608
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83230 PLASTIC TETRAFLUOR TFC616
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83231 PLASTIC TETRAFLUOR TFC617
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83232 PLASTIC TETRAFLUOR TFC618
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83233 PLASTIC TETRALON
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006273 8

Information Handling Services, 2000

83234 PLASTIC TETRALON 510
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83235 PLASTIC TETRALON 710
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83236 PLASTIC TETRALON TFC031
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83237 PLASTIC TETRALON TFC033
MANF: TETRAFLUOR
....NO TEST DATA AVAILABLE....

83354 PLASTIC TEXALON 1106A
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83355 PLASTIC TEXALON 1108A
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83356 PLASTIC TEXALON 1110 AL PL2 HS BK18
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83357 PLASTIC TEXALON 1200A
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83358 PLASTIC TEXALON 1200A FR
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83359 PLASTIC TEXALON 1200A HS
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83360 PLASTIC TEXALON 1200A ZIP
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83361 PLASTIC TEXALON 1200A ZIP 10
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83362 PLASTIC TEXALON 1200A ZIP 10 BX11
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83363 PLASTIC TEXALON 1203D ZIP 10
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006274 T ■

Information Handling Services, 2000

83364 PLASTIC TEXALON 1308A
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83365 PLASTIC TEXALON 1310
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83366 PLASTIC TEXALON 600A
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83367 PLASTIC TEXALON 600A HS
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83368 PLASTIC TEXALON 600A HV HS
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83369 PLASTIC TEXALON 600A PL2
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83370 PLASTIC TEXALON 600A ZIP
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83371 PLASTIC TEXALON 600A ZIP 10
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83372 PLASTIC TEXALON 623 HS BK13
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83373 PLASTIC TEXALON 680A
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83374 PLASTIC TEXALON GF 1200 A33
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83375 PLASTIC TEXALON GF 1308 A13
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83376 PLASTIC TEXALON GF 1310-13
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83377 PLASTIC TEXALON GF 600 A33
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006275 1 ■

Information Handling Services, 2000

83378 PLASTIC TEXALON GMF 600-40
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83379 PLASTIC TEXALON MF 1200A-40
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83380 PLASTIC TEXALON MF 1200A1-40
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83382 PLASTIC TEXALON MF 600-40
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83383 PLASTIC TEXALON XP1296
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83384 PLASTIC TEXALON XP1317
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

83385 PLASTIC TEXALON XP1319 HS
MANF: TEXAPOL
....NO TEST DATA AVAILABLE....

69736 PLASTIC TFE FLUOROCARBON
MANF: CURBELL
....NO TEST DATA AVAILABLE....

82380 PLASTIC THERMALUX UDEL POLYSULFONE
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

83084 PLASTIC THERMOCOMP AF-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83261 PLASTIC THERMOCOMP AF-1006
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.20	.01	.00		No test data		

83264 PLASTIC THERMOCOMP AF-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83265 PLASTIC THERMOCOMP BF-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83267 PLASTIC THERMOCOMP BF-1006
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.24	.01	.00		No test data		

MSFC-HDBK-527 REV F 9999942 0006276 3

Information Handling Services, 2000

83268 PLASTIC THERMOCOMP BF-1006FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83270 PLASTIC THERMOCOMP BF-1007
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83271 PLASTIC THERMOCOMP BF-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83273 PLASTIC THERMOCOMP CF-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83275 PLASTIC THERMOCOMP CF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83277 PLASTIC THERMOCOMP DC-1003FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83280 PLASTIC THERMOCOMP DC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83282 PLASTIC THERMOCOMP DC-1006PC
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83284 PLASTIC THERMOCOMP DF-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83285 PLASTIC THERMOCOMP DF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83286 PLASTIC THERMOCOMP DF-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83288 PLASTIC THERMOCOMP DFA-113
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83290 PLASTIC THERMOCOMP DFL-4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83292 PLASTIC THERMOCOMP DL-4020FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006277 5

Information Handling Services, 2000

83294 PLASTIC THERMOCOMP DL-4030
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83297 PLASTIC THERMOCOMP EC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83300 PLASTIC THERMOCOMP EC-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83302 PLASTIC THERMOCOMP EF-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83304 PLASTIC THERMOCOMP EF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83305 PLASTIC THERMOCOMP EF-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83308 PLASTIC THERMOCOMP EFL-4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83311 PLASTIC THERMOCOMP FC-102CF
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83312 PLASTIC THERMOCOMP FF-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83313 PLASTIC THERMOCOMP FF-1006
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.13	.03	.00		No test data		

83314 PLASTIC THERMOCOMP FF-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83315 PLASTIC THERMOCOMP FP-EC-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83316 PLASTIC THERMOCOMP FP-PC-1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83317 PLASTIC THERMOCOMP FP-VC-1003
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006278 7

Information Handling Services, 2000

84113 PLASTIC THERMOCOMP FS-100-10
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83318 PLASTIC THERMOCOMP FULTON 441
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83319 PLASTIC THERMOCOMP FULTON 441D
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83332 PLASTIC THERMOCOMP GC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83335 PLASTIC THERMOCOMP GF-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83336 PLASTIC THERMOCOMP GF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83341 PLASTIC THERMOCOMP GF-1006FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83344 PLASTIC THERMOCOMP GF-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83346 PLASTIC THERMOCOMP HF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83351 PLASTIC THERMOCOMP IC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83532 PLASTIC THERMOCOMP IF-100-10
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83534 PLASTIC THERMOCOMP IF-100-12
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83537 PLASTIC THERMOCOMP IF-1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83539 PLASTIC THERMOCOMP IF-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006279 9 ■

Information Handling Services, 2000

83542 PLASTIC THERMOCOMP IF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83543 PLASTIC THERMOCOMP IF-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83545 PLASTIC THERMOCOMP JC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83546 PLASTIC THERMOCOMP JCL-4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83548 PLASTIC THERMOCOMP JF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83550 PLASTIC THERMOCOMP KB-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83552 PLASTIC THERMOCOMP KC-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83554 PLASTIC THERMOCOMP KF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83555 PLASTIC THERMOCOMP KFX-1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83556 PLASTIC THERMOCOMP KFX-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83557 PLASTIC THERMOCOMP KFX-1008MG
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83559 PLASTIC THERMOCOMP MF-1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83560 PLASTIC THERMOCOMP MF-1002HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83562 PLASTIC THERMOCOMP MF-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006280 5 ■

Information Handling Services, 2000

83566 PLASTIC THERMOCOMP MF-1004FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83564 PLASTIC THERMOCOMP MF-1004HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83568 PLASTIC THERMOCOMP MF-1004HS
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83570 PLASTIC THERMOCOMP MF-1006
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.13	.04	.00		No test data		

83575 PLASTIC THERMOCOMP MF-1006HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83573 PLASTIC THERMOCOMP MF-1006HS
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83577 PLASTIC THERMOCOMP MF-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83578 PLASTIC THERMOCOMP MF-1008HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83581 PLASTIC THERMOCOMP MF-1008HS
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83583 PLASTIC THERMOCOMP MFX-1004HS
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83586 PLASTIC THERMOCOMP MFX-1006HS
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83588 PLASTIC THERMOCOMP MFX-1008HS
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83591 PLASTIC THERMOCOMP MOS2 LUBED NYLON
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83594 PLASTIC THERMOCOMP MF1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006281 7

83598 PLASTIC THERMOCOMP NF1006
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.11	.01	.00		No test data		

83599 PLASTIC THERMOCOMP NF1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83600 PLASTIC THERMOCOMP OC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83601 PLASTIC THERMOCOMP OCL-4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83602 PLASTIC THERMOCOMP OF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83603 PLASTIC THERMOCOMP OF-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83604 PLASTIC THERMOCOMP OFL-4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83605 PLASTIC THERMOCOMP PC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83606 PLASTIC THERMOCOMP PDX-79738
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84042 PLASTIC THERMOCOMP PDX-81319
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84043 PLASTIC THERMOCOMP PF-100-10
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84044 PLASTIC THERMOCOMP PF-100-12
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84045 PLASTIC THERMOCOMP PF-1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84046 PLASTIC THERMOCOMP PF-1002HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006282 9

Information Handling Services, 2000

84047 PLASTIC THERMOCOMP PF-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84048 PLASTIC THERMOCOMP PF-1004HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84049 PLASTIC THERMOCOMP PF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84051 PLASTIC THERMOCOMP PF-1006FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84050 PLASTIC THERMOCOMP PF-1006HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84052 PLASTIC THERMOCOMP PF-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84053 PLASTIC THERMOCOMP PF-1008HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84054 PLASTIC THERMOCOMP PFL-4216
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84055 PLASTIC THERMOCOMP PFL-4218
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84056 PLASTIC THERMOCOMP QC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84057 PLASTIC THERMOCOMP QF-100-10
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84058 PLASTIC THERMOCOMP QF-100-12
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84059 PLASTIC THERMOCOMP QF-1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84060 PLASTIC THERMOCOMP QF-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006283 0

Information Handling Services, 2000

84061 PLASTIC THERMOCOMP QF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84062 PLASTIC THERMOCOMP QF-1006FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84063 PLASTIC THERMOCOMP QF-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84065 PLASTIC THERMOCOMP R1000 FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84064 PLASTIC THERMOCOMP R1000 FR HS
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84066 PLASTIC THERMOCOMP RC-1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84067 PLASTIC THERMOCOMP RC-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84084 PLASTIC THERMOCOMP RC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84088 PLASTIC THERMOCOMP RC-1006HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84090 PLASTIC THERMOCOMP RC-1006PC
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84092 PLASTIC THERMOCOMP RC-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84093 PLASTIC THERMOCOMP RCL-4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84094 PLASTIC THERMOCOMP RCL-4536
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84095 PLASTIC THERMOCOMP RF-100-10
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006284 2

Information Handling Services, 2000

84096 PLASTIC THERMOCOMP RF-100-12
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84097 PLASTIC THERMOCOMP RF-1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84098 PLASTIC THERMOCOMP RF-1002HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84099 PLASTIC THERMOCOMP RF-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84101 PLASTIC THERMOCOMP RF-1004FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84102 PLASTIC THERMOCOMP RF-1004FR HS
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84100 PLASTIC THERMOCOMP RF-1004HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84103 PLASTIC THERMOCOMP RF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84105 PLASTIC THERMOCOMP RF-1006FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84104 PLASTIC THERMOCOMP RF-1006HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84106 PLASTIC THERMOCOMP RF-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84107 PLASTIC THERMOCOMP RF-1008HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84108 PLASTIC THERMOCOMP RFL-4216
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84109 PLASTIC THERMOCOMP RFL-4218
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006285 4

Information Handling Services, 2000

84110 PLASTIC THERMOCOMP RL-4310
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84114 PLASTIC THERMOCOMP SF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84115 PLASTIC THERMOCOMP STAT-KON D
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84117 PLASTIC THERMOCOMP STYPRENIC
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84119 PLASTIC THERMOCOMP UF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84125 PLASTIC THERMOCOMP UNFORTIFIED NYLON 11
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84127 PLASTIC THERMOCOMP UNFORTIFIED NYLON 12
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84129 PLASTIC THERMOCOMP UNFORTIFIED NYLON 6
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84123 PLASTIC THERMOCOMP UNFORTIFIED NYLON 6/10
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.65	.04	.00		No test data		

84131 PLASTIC THERMOCOMP UNFORTIFIED NYLON 6/12
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84133 PLASTIC THERMOCOMP UNFORTIFIED NYLON 6/6
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84134 PLASTIC THERMOCOMP VC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84135 PLASTIC THERMOCOMP WC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84136 PLASTIC THERMOCOMP WF-1002
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006286 6

Information Handling Services, 2000

84137 PLASTIC THERMOCOMP WF-1002HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84139 PLASTIC THERMOCOMP WF-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84140 PLASTIC THERMOCOMP WF-1004HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84141 PLASTIC THERMOCOMP WF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84143 PLASTIC THERMOCOMP WF-1006FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84142 PLASTIC THERMOCOMP WF-1006HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84145 PLASTIC THERMOCOMP WF-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84146 PLASTIC THERMOCOMP WF-1008HI
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84147 PLASTIC THERMOCOMP XC-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84148 PLASTIC THERMOCOMP XF-1004
MANF: L N P CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.06	.01	.00		No test data		

84149 PLASTIC THERMOCOMP XF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84150 PLASTIC THERMOCOMP XFL-4036
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84023 PLASTIC THERMOCOMP ZF-1004
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84024 PLASTIC THERMOCOMP ZF-1006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006287 8

84025 PLASTIC THERMOCOMP ZF-1008
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

83386 PLASTIC THERMOFIL A 20FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83387 PLASTIC THERMOFIL A 35FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83388 PLASTIC THERMOFIL A1 20FG0570
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83389 PLASTIC THERMOFIL A1 20FG0700
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83390 PLASTIC THERMOFIL B 20FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83391 PLASTIC THERMOFIL B 35FB0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83392 PLASTIC THERMOFIL B 35FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83393 PLASTIC THERMOFIL D 10FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83394 PLASTIC THERMOFIL D 20FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83395 PLASTIC THERMOFIL D 20FG0500
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83396 PLASTIC THERMOFIL D 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83397 PLASTIC THERMOFIL D 9900-6500
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83398 PLASTIC THERMOFIL E 15FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006288 T

Information Handling Services, 2000

83399 PLASTIC THERMOFIL E 15FG0590
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83400 PLASTIC THERMOFIL E 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83416 PLASTIC THERMOFIL E 30FG0287
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83401 PLASTIC THERMOFIL E 30FG0590
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83402 PLASTIC THERMOFIL E 30HF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83403 PLASTIC THERMOFIL E 40FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83404 PLASTIC THERMOFIL E 40MI0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83405 PLASTIC THERMOFIL E 45FM0319
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83406 PLASTIC THERMOFIL E 45FM0393
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83407 PLASTIC THERMOFIL E 9900-0590
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83408 PLASTIC THERMOFIL E1 10FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83409 PLASTIC THERMOFIL E1 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83410 PLASTIC THERMOFIL E1 30FG0584
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83411 PLASTIC THERMOFIL E2 30FG0100/E2 30FG0578
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006289 1

83412 PLASTIC THERMOFIL E2 30FG7100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83413 PLASTIC THERMOFIL E2 30NF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83414 PLASTIC THERMOFIL E2 45FM0393
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83415 PLASTIC THERMOFIL E2 55FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83417 PLASTIC THERMOFIL F 10FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83418 PLASTIC THERMOFIL F 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83419 PLASTIC THERMOFIL G 20FG0214
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83420 PLASTIC THERMOFIL G 20NF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83421 PLASTIC THERMOFIL G 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83423 PLASTIC THERMOFIL G 900-0257
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83422 PLASTIC THERMOFIL G 9900-0215
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83424 PLASTIC THERMOFIL K 20FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83425 PLASTIC THERMOFIL K 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83426 PLASTIC THERMOFIL K 30FG0214
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006290 8

Information Handling Services, 2000

83427 PLASTIC THERMOFIL K 30NF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83428 PLASTIC THERMOFIL K2 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83429 PLASTIC THERMOFIL K2 30NF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83430 PLASTIC THERMOFIL L 20FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83431 PLASTIC THERMOFIL L 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83432 PLASTIC THERMOFIL L1 30FG0580
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83433 PLASTIC THERMOFIL N 15FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83434 PLASTIC THERMOFIL N 15FG0500
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83435 PLASTIC THERMOFIL N 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83436 PLASTIC THERMOFIL N 30FG0214
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83437 PLASTIC THERMOFIL N 30FG05[illegible]0
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83438 PLASTIC THERMOFIL N 30NF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83439 PLASTIC THERMOFIL N 40BG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83440 PLASTIC THERMOFIL N 40FM0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006291 T ■

Information Handling Services, 2000

83441 PLASTIC THERMOFIL N 40MF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83442 PLASTIC THERMOFIL N 9900-0500
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83443 PLASTIC THERMOFIL N11 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83444 PLASTIC THERMOFIL N11 30NF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83445 PLASTIC THERMOFIL N11 40MF0350
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83446 PLASTIC THERMOFIL N12 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83447 PLASTIC THERMOFIL N12 30FG0282
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83448 PLASTIC THERMOFIL N12 30FG0500
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83449 PLASTIC THERMOFIL N12 30NF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83450 PLASTIC THERMOFIL N3 13FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83451 PLASTIC THERMOFIL N3 13FG0700
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83452 PLASTIC THERMOFIL N3 15FG0560
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83453 PLASTIC THERMOFIL N3 20NF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83454 PLASTIC THERMOFIL N3 30FG0214
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006292 1 ■

Information Handling Services, 2000

83455 PLASTIC THERMOFIL N3 30FG0231
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83457 PLASTIC THERMOFIL N3 30FG0560
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83456 PLASTIC THERMOFIL N3 30FR0282
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83458 PLASTIC THERMOFIL N3 30NF0214
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83459 PLASTIC THERMOFIL N3 33FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83460 PLASTIC THERMOFIL N3 33FG0700
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83461 PLASTIC THERMOFIL N3 35FM0310
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83462 PLASTIC THERMOFIL N3 40MF0350
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83463 PLASTIC THERMOFIL N3 40MF8300
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83464 PLASTIC THERMOFIL N3 40NF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83465 PLASTIC THERMOFIL N3 43FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83466 PLASTIC THERMOFIL N3 9900-0200
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83467 PLASTIC THERMOFIL N3 9900-0214
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83468 PLASTIC THERMOFIL N3 9900-0231
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006293 3

Information Handling Services, 2000

83469 PLASTIC THERMOFIL N3 9900-0279
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83470 PLASTIC THERMOFIL N3 9900-0560
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83471 PLASTIC THERMOFIL N5 15FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83472 PLASTIC THERMOFIL N5 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83473 PLASTIC THERMOFIL N6 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83474 PLASTIC THERMOFIL N6 30FG0214
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83475 PLASTIC THERMOFIL N6 30FG0282
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83476 PLASTIC THERMOFIL N6 30FG0500
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83477 PLASTIC THERMOFIL N6 30NF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83478 PLASTIC THERMOFIL N6 9900-0500
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83479 PLASTIC THERMOFIL N7 13FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83480 PLASTIC THERMOFIL N7 20FG0500
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83481 PLASTIC THERMOFIL N7 20NF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83482 PLASTIC THERMOFIL N7 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006294 5 ■

Information Handling Services, 2000

83483 PLASTIC THERMOFIL N7 35MF7365
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83484 PLASTIC THERMOFIL N7 9900-0500
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83485 PLASTIC THERMOFIL N8 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83486 PLASTIC THERMOFIL N9 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83487 PLASTIC THERMOFIL P 10FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83488 PLASTIC THERMOFIL P 20FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83489 PLASTIC THERMOFIL P 20FG0500
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83490 PLASTIC THERMOFIL P 20FG0720
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83491 PLASTIC THERMOFIL P 20MF0500
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83492 PLASTIC THERMOFIL P 20MI0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83493 PLASTIC THERMOFIL P 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83494 PLASTIC THERMOFIL P 40CC0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83495 PLASTIC THERMOFIL P 40CC0720
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83496 PLASTIC THERMOFIL P 40MI0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006295 7

83497 PLASTIC THERMOFIL P 40MI0720
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83498 PLASTIC THERMOFIL P 40TC0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83499 PLASTIC THERMOFIL P 9900-0500
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83500 PLASTIC THERMOFIL P 9900-0570
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83501 PLASTIC THERMOFIL P1 10FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83502 PLASTIC THERMOFIL P1 20FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83503 PLASTIC THERMOFIL P1 20FG0720
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83504 PLASTIC THERMOFIL P1 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83505 PLASTIC THERMOFIL P6 10FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83506 PLASTIC THERMOFIL P6 20FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83507 PLASTIC THERMOFIL P6 20FG0500
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83508 PLASTIC THERMOFIL P6 20FG0570
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83509 PLASTIC THERMOFIL P6 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83510 PLASTIC THERMOFIL P6 30FG0720
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006296 9

Information Handling Services, 2000

83511 PLASTIC THERMOFIL R 10FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83512 PLASTIC THERMOFIL R 10FG0568
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83513 PLASTIC THERMOFIL R 20MF0214
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83514 PLASTIC THERMOFIL R 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83515 PLASTIC THERMOFIL R 30FG0214
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83516 PLASTIC THERMOFIL R 30FG0568
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83517 PLASTIC THERMOFIL R 40MF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83518 PLASTIC THERMOFIL R 9900-0200
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83519 PLASTIC THERMOFIL R 9900-0214
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83520 PLASTIC THERMOFIL R2 10FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83521 PLASTIC THERMOFIL R2 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83522 PLASTIC THERMOFIL S 20FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83523 PLASTIC THERMOFIL S 30FG0214
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83524 PLASTIC THERMOFIL S 30MF0360
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

83607 PLASTIC THERMOFIL S 30NF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83608 PLASTIC THERMOFIL S 40FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83609 PLASTIC THERMOFIL T 20NF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83610 PLASTIC THERMOFIL T 30FG0214
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83611 PLASTIC THERMOFIL T 30NF0214
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83612 PLASTIC THERMOFIL T 40FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83613 PLASTIC THERMOFIL T 40NF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83614 PLASTIC THERMOFIL T 40NG0948
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83615 PLASTIC THERMOFIL T 50CG0940
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83616 PLASTIC THERMOFIL T 50FM0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83617 PLASTIC THERMOFIL U 10FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83618 PLASTIC THERMOFIL V 10FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83619 PLASTIC THERMOFIL V 20FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83620 PLASTIC THERMOFIL V 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006298 2 ■

Information Handling Services, 2000

83621 PLASTIC THERMOFIL W 10FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83622 PLASTIC THERMOFIL W 30FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83623 PLASTIC THERMOFIL W 30NF0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83624 PLASTIC THERMOFIL W 30NF0214
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83625 PLASTIC THERMOFIL Y 20FG0100
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83626 PLASTIC THERMOFIL Y 20FG0500
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

83627 PLASTIC THERMOFIL Y7 9900-6500
MANF: THERMOFIL
....NO TEST DATA AVAILABLE....

82509 PLASTIC TIFFAK A
MANF: ROHM & HAAS
....NO TEST DATA AVAILABLE....

69743 PLASTIC TITANIUM PUTTY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

05208 PLASTIC TORLON 4203 GID: DKCDAR
MANF: AMOCO
POLYMER CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.075			00.20	NONE
A	1	030.0	009.0	0.125			00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	112	40	125	0.040	0	20
C	MECH	150	50	100	0.040	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.95	.01	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00021.38	

20753 PLASTIC TORLON 4301 POLYIMIDE-AMIDE GID: DKCDAR
MANF: AMOCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.081			00.20	NONE
A	1	025.9	014.3	0.187			00.25	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.0E-6	1.16	.01		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00021.42	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006299 4

68575 PLASTIC TORLON 5030
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

67698 PLASTIC TP-901 HARDSET TOOLING PASTE
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67710 PLASTIC TP-903 HARDSET TOOLING PASTE
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67709 PLASTIC TP-906 HARDSET TOOLING PASTE
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67708 PLASTIC TP908 CARVABLE TOOLING PASTE
MANF: AKEMI PLASTICS
....NO TEST DATA AVAILABLE....

67968 PLASTIC TPR1720D
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67967 PLASTIC TPR1900D
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67959 PLASTIC TPR5190
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67960 PLASTIC TPR5260
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67961 PLASTIC TPR5280
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67962 PLASTIC TPR5290
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67963 PLASTIC TPR5470
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67964 PLASTIC TPR5490
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

67966 PLASTIC TPR5591
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006300 7 ■

Information Handling Services, 2000

67965 PLASTIC TPR5595
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

84761 PLASTIC TPR5680
MANF: BP PERFORMANCE POLYMERS, INC
....NO TEST DATA AVAILABLE....

84650 PLASTIC TRIAZ 1120
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84654 PLASTIC TRIAZ 1125
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

68547 PLASTIC TROGAMID
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

84819 PLASTIC TYRIL 1000
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84829 PLASTIC TYRIL 1000B
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84830 PLASTIC TYRIL 1020
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84832 PLASTIC TYRIL 1021
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84833 PLASTIC TYRIL 1031
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84834 PLASTIC TYRIL 880
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84835 PLASTIC TYRIL 880B
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

83679 PLASTIC UBE NYLON 1011FB
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83680 PLASTIC UBE NYLON 1011GC4
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006301 9

83681 PLASTIC UBE NYLON 1013B
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83682 PLASTIC UBE NYLON 1013NB
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83683 PLASTIC UBE NYLON 1013NH
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83684 PLASTIC UBE NYLON 1013NU2
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83685 PLASTIC UBE NYLON 1013NW8
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83686 PLASTIC UBE NYLON 1013R
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83687 PLASTIC UBE NYLON 1013RU1
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83688 PLASTIC UBE NYLON 1013RW
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83689 PLASTIC UBE NYLON 1015G1
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83690 PLASTIC UBE NYLON 1015GC6
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83691 PLASTIC UBE NYLON 1015GC9
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83692 PLASTIC UBE NYLON 10181
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83693 PLASTIC UBE NYLON 1022B
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83694 PLASTIC UBE NYLON 1022SV2
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006302 0 ■

Information Handling Services, 2000

83695 PLASTIC UBE NYLON 1030B
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83696 PLASTIC UBE NYLON 1030J
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83697 PLASTIC UBE NYLON 1030QB
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83698 PLASTIC UBE NYLON 2015B
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83699 PLASTIC UBE NYLON 2015SV
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83700 PLASTIC UBE NYLON 2020B
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83701 PLASTIC UBE NYLON 2020GC4
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83702 PLASTIC UBE NYLON 2020GC6
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83703 PLASTIC UBE NYLON 2020GC9
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83706 PLASTIC UBE NYLON 2020U
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83707 PLASTIC UBE NYLON 2020UW1
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83708 PLASTIC UBE NYLON 3014U
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83709 PLASTIC UBE NYLON 3020LU1
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83710 PLASTIC UBE NYLON 3024LU
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006303 2

83711 PLASTIC UBE NYLON 3024U
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83704 PLASTIC UBE NYLON 3030GCU
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83705 PLASTIC UBE NYLON 3030H
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83712 PLASTIC UBE NYLON 3035JL1
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83713 PLASTIC UBE NYLON 3035JU
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83714 PLASTIC UBE NYLON 3035JU6
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83715 PLASTIC UBE NYLON 3035LU
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83716 PLASTIC UBE NYLON 3035U
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83718 PLASTIC UBE NYLON 5033J12
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83719 PLASTIC UBE NYLON UMC1
MANF: UBE INDUSTRIES
....NO TEST DATA AVAILABLE....

83725 PLASTIC UCAR DFDA1137 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83726 PLASTIC UCAR DFDA1138 NATURAL
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

83727 PLASTIC UDEL POLYSULFONE P1700 CL2611
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

63949 PLASTIC ULTEM 1000 GID: BPCDXX
MANF: GENERAL ELECTRIC

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	030.0	010.0	0.010			00.60	SMALL	No test data		No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006304 4

63949 PLASTIC ULTEM 1000 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	030.0	010.0	0.010		00.10	12.00	T SMALL

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.96	.00	.40	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00022.71	

69453 PLASTIC ULTEM 1010
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

68577 PLASTIC ULTEM 2100
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

68589 PLASTIC ULTEM 2200
MANF: DIXON INDUSTRIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.63	.00	.30	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

68578 PLASTIC ULTEM 2300
MANF: DIXON INDUSTRIES
....NO TEST DATA AVAILABLE....

69455 PLASTIC ULTEM 2400
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69464 PLASTIC ULTEM 4000
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69458 PLASTIC ULTEM 4001
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69462 PLASTIC ULTEM 6000
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE. ..

69456 PLASTIC ULTEM 6100
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69463 PLASTIC ULTEM 6200
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69457 PLASTIC ULTEM 6202
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69555 PLASTIC ULTRA-WEAR UHMPE
MANF: GULF WANDES
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006305 6

85247 PLASTIC ULTRA-WEAR UHMUPE
MANF: POLYMER CORP
....NO TEST DATA AVAILABLE....

80903 PLASTIC ULTRADUR B4300G2
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80904 PLASTIC ULTRADUR B4300G4
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80905 PLASTIC ULTRADUR B4300G6
MANF: BASF STRUCTURAL MATERIALS

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.16	.00	.08		No test data		

80906 PLASTIC ULTRADUR B4305G6
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80907 PLASTIC ULTRADUR B4500
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80908 PLASTIC ULTRADUR B4520
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80909 PLASTIC ULTRADUR KR4015
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80910 PLASTIC ULTRADUR KR4025
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80911 PLASTIC ULTRADUR KR4035
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80912 PLASTIC ULTRADUR KR4300K4
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80913 PLASTIC ULTRAFORM H2200G5
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80914 PLASTIC ULTRAFORM H2320
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80915 PLASTIC ULTRAFORM N2320
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006306 8

Information Handling Services, 2000

80916 PLASTIC ULTRAFORM S2320
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80917 PLASTIC ULTRAFORM W2320
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80918 PLASTIC ULTRAMID A25
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80919 PLASTIC ULTRAMID A3
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80938 PLASTIC ULTRAMID A3 X 1G5
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80939 PLASTIC ULTRAMID A3 X 1G7
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80940 PLASTIC ULTRAMID A3 X G5
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80941 PLASTIC ULTRAMID A3 X G7
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80920 PLASTIC ULTRAMID A3EG10
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80921 PLASTIC ULTRAMID A3EG5
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80922 PLASTIC ULTRAMID A3EG6
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80923 PLASTIC ULTRAMID A3EG7
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80924 PLASTIC ULTRAMID A3G10
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80926 PLASTIC ULTRAMID A3G6
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006307 T

80927 PLASTIC ULTRAMID A3G7
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80925 PLASTIC ULTRAMID A3GA
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80928 PLASTIC ULTRAMID A3HG5
MANF: BASF STRUCTURAL MATERIALS

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.35	.04	.00		No test data		

80929 PLASTIC ULTRAMID A3K
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80930 PLASTIC ULTRAMID A3KH
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80931 PLASTIC ULTRAMID A3R
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80932 PLASTIC ULTRAMID A3SK
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80933 PLASTIC ULTRAMID A3W
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80934 PLASTIC ULTRAMID A3WG10
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80935 PLASTIC ULTRAMID A3WG5
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80936 PLASTIC ULTRAMID A3WG6
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80937 PLASTIC ULTRAMID A3WG7
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80942 PLASTIC ULTRAMID A4
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80943 PLASTIC ULTRAMID A4H
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006308 1

Information Handling Services, 2000

80944 PLASTIC ULTRAMID A4K
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80945 PLASTIC ULTRAMID A5
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80946 PLASTIC ULTRAMID B3
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80947 PLASTIC ULTRAMID B35
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80948 PLASTIC ULTRAMID B35G3
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80949 PLASTIC ULTRAMID B35SK
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80950 PLASTIC ULTRAMID B35W
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80951 PLASTIC ULTRAMID B3EG10
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80952 PLASTIC ULTRAMID B3EG5
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80953 PLASTIC ULTRAMID B3EG6
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80954 PLASTIC ULTRAMID B3EG7
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80955 PLASTIC ULTRAMID B3G10
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80956 PLASTIC ULTRAMID B3G5
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80957 PLASTIC ULTRAMID B3G5HS
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006309 3

80958 PLASTIC ULTRAMID B3G6
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80959 PLASTIC ULTRAMID B3G6HS
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80960 PLASTIC ULTRAMID B3G7
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80961 PLASTIC ULTRAMID B3G7HS
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80962 PLASTIC ULTRAMID B3K
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80963 PLASTIC ULTRAMID B3L
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80964 PLASTIC ULTRAMID B3S
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80965 PLASTIC ULTRAMID B3WG10
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80966 PLASTIC ULTRAMID B3WG5
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80967 PLASTIC ULTRAMID B3WG6
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80968 PLASTIC ULTRAMID B3WG7
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80969 PLASTIC ULTRAMID B4
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80970 PLASTIC ULTRAMID B4K
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80971 PLASTIC ULTRAMID B5
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006310 T

Information Handling Services, 2000

80972 PLASTIC ULTRAMID B5W
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80973 PLASTIC ULTRAMID KR1421
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80989 PLASTIC ULTRAMID KR4442/300
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80974 PLASTIC ULTRAMID KR4600
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80988 PLASTIC ULTRAMID KR4601
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80990 PLASTIC ULTRAMID S3
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80991 PLASTIC ULTRAMID S3K
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80992 PLASTIC ULTRAMID S4
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

84837 PLASTIC ULTRATHENE UE 631 19% VA
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84841 PLASTIC ULTRATHENE UE 633 19% VA
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84843 PLASTIC ULTRATHENE UE 635 9% VA
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84845 PLASTIC ULTRATHENE UE 637 9% VA
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84847 PLASTIC ULTRATHENE UE 655 9% VA
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

84853 PLASTIC ULTRATHENE UE 657 12% VA
MANF: NATIONAL DISTILLERS & CHEMICAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006311 1

83946 PLASTIC ULTRATHENE UE630 17% VA
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83941 PLASTIC ULTRATHENE UE634 28% VA
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83942 PLASTIC ULTRATHENE UE645 28% VA
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83943 PLASTIC ULTRATHENE UE648 19% VA
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83944 PLASTIC ULTRATHENE UE656-03 12% VA
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

83945 PLASTIC ULTRATHENE UE658 12% VA
MANF: USI CHEMICALS
....NO TEST DATA AVAILABLE....

68162 PLASTIC UNICHEM 10015-XRAY
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

84340 PLASTIC UNICHEM 1010G015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68221 PLASTIC UNICHEM 1011G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

84341 PLASTIC UNICHEM 1011G05
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68220 PLASTIC UNICHEM 1015G-05
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

84342 PLASTIC UNICHEM 1015G015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68087 PLASTIC UNICHEM 105
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68290 PLASTIC UNICHEM 1080G
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006312 3 ■

Information Handling Services, 2000

68133 PLASTIC UNICHEM 1104
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68219 PLASTIC UNICHEM 1104-05
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68134 PLASTIC UNICHEM 1114
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68218 PLASTIC UNICHEM 1114G-05
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68217 PLASTIC UNICHEM 1115G-05
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68135 PLASTIC UNICHEM 1116
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68114 PLASTIC UNICHEM 1116G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68216 PLASTIC UNICHEM 1280A-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68097 PLASTIC UNICHEM 1280G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

84343 PLASTIC UNICHEM 1304-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68291 PLASTIC UNICHEM 1304G
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68289 PLASTIC UNICHEM 1314 NATURAL
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68288 PLASTIC UNICHEM 1316-05
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68287 PLASTIC UNICHEM 1317
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

68286 PLASTIC UNICHEM 1416-05
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68157 PLASTIC UNICHEM 3876
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68156 PLASTIC UNICHEM 3879
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68065 PLASTIC UNICHEM 40-105
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68116 PLASTIC UNICHEM 4011
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68098 PLASTIC UNICHEM 4012G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68061 PLASTIC UNICHEM 4060
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68062 PLASTIC UNICHEM 4060A
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68063 PLASTIC UNICHEM 4075
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68064 PLASTIC UNICHEM 4075H
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68155 PLASTIC UNICHEM 4075H FR
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68066 PLASTIC UNICHEM 4114
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68069 PLASTIC UNICHEM 4160
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68071 PLASTIC UNICHEM 4160 LT/FR-1
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006314 7 ■

Information Handling Services, 2000

68070 PLASTIC UNICHEM 4160C
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68153 PLASTIC UNICHEM 4160LT
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68215 PLASTIC UNICHEM 4170
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68067 PLASTIC UNICHEM 4195
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68151 PLASTIC UNICHEM 4196
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68072 PLASTIC UNICHEM 4260-75
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68073 PLASTIC UNICHEM 4260-80
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68146 PLASTIC UNICHEM 4260-85
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68074 PLASTIC UNICHEM 4260-90
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68150 PLASTIC UNICHEM 4260-95
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68147 PLASTIC UNICHEM 4260A-66
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

84344 PLASTIC UNICHEM 4261-40
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68145 PLASTIC UNICHEM 4261-80
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68214 PLASTIC UNICHEM 4511
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006315 9

Information Handling Services, 2000

68039 PLASTIC UNICHEM 4543
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68040 PLASTIC UNICHEM 4875
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68117 PLASTIC UNICHEM 5011
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68099 PLASTIC UNICHEM 5012G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68213 PLASTIC UNICHEM 5012G-05
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68285 PLASTIC UNICHEM 5160-40
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68212 PLASTIC UNICHEM 5211
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68093 PLASTIC UNICHEM 5311-38
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68088 PLASTIC UNICHEM 5376
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68148 PLASTIC UNICHEM 5376FFR
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68068 PLASTIC UNICHEM 5433
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68284 PLASTIC UNICHEM 5500
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68118 PLASTIC UNICHEM 5511
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68210 PLASTIC UNICHEM 5511-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006316 0 ■

68041 PLASTIC UNICHEM 5543
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68042 PLASTIC UNICHEM 5545
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

84345 PLASTIC UNICHEM 5611
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68209 PLASTIC UNICHEM 5612
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68043 PLASTIC UNICHEM 5790
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68281 PLASTIC UNICHEM 5790A
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68208 PLASTIC UNICHEM 5811
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68094 PLASTIC UNICHEM 5812
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68119 PLASTIC UNICHEM 6011
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68207 PLASTIC UNICHEM 6011A-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68206 PLASTIC UNICHEM 6011G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68100 PLASTIC UNICHEM 6012G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68205 PLASTIC UNICHEM 6014 D FOAM
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68204 PLASTIC UNICHEM 6022 NATURAL
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006317 2

Information Handling Services, 2000

68280 PLASTIC UNICHEM 6033
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68279 PLASTIC UNICHEM 6091
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68275 PLASTIC UNICHEM 6093
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68203 PLASTIC UNICHEM 6111A
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68202 PLASTIC UNICHEM 6111B
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68149 PLASTIC UNICHEM 6193F
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68278 PLASTIC UNICHEM 6283
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68091 PLASTIC UNICHEM 6476
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68277 PLASTIC UNICHEM 6500
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68276 PLASTIC UNICHEM 6507
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68120 PLASTIC UNICHEM 6511
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68201 PLASTIC UNICHEM 6511-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68200 PLASTIC UNICHEM 6511A-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68199 PLASTIC UNICHEM 6512
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006318 4

Information Handling Services, 2000

68101 PLASTIC UNICHEM 6512G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68274 PLASTIC UNICHEM 6574
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68044 PLASTIC UNICHEM 6575
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68273 PLASTIC UNICHEM 6576
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68055 PLASTIC UNICHEM 6742
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68056 PLASTIC UNICHEM 6743
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68272 PLASTIC UNICHEM 6743 CLEAR
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68121 PLASTIC UNICHEM 6811
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68198 PLASTIC UNICHEM 6811-02 BUSCH
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68197 PLASTIC UNICHEM 6812-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68271 PLASTIC UNICHEM 6812A-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68102 PLASTIC UNICHEM 6812G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68033 PLASTIC UNICHEM 7000
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68269 PLASTIC UNICHEM 7003
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006319 6

Information Handling Services, 2000

DATE: 12/23/88
NON-METALS BY DESIGNATION

68270 PLASTIC UNICHEM 7003 WHITE
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68122 PLASTIC UNICHEM 7011
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68195 PLASTIC UNICHEM 7011CZ-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68196 PLASTIC UNICHEM 7011G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68095 PLASTIC UNICHEM 7012
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68194 PLASTIC UNICHEM 7012C-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68103 PLASTIC UNICHEM 7012G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68050 PLASTIC UNICHEM 7033
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68267 PLASTIC UNICHEM 7074
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68045 PLASTIC UNICHEM 7075
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

84346 PLASTIC UNICHEM 7090B
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68193 PLASTIC UNICHEM 7099
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68264 PLASTIC UNICHEM 7224B
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68263 PLASTIC UNICHEM 7233
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006320 2

Information Handling Services, 2000

68192 PLASTIC UNICHEM 7233H
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68262 PLASTIC UNICHEM 7305
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68057 PLASTIC UNICHEM 7342
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68261 PLASTIC UNICHEM 7342 CLEAR
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68260 PLASTIC UNICHEM 7380 CLEAR
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68191 PLASTIC UNICHEM 7411-0
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68089 PLASTIC UNICHEM 7444
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68090 PLASTIC UNICHEM 7444D
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68224 PLASTIC UNICHEM 75-103B
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68034 PLASTIC UNICHEM 7500
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68257 PLASTIC UNICHEM 7503
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68123 PLASTIC UNICHEM 7511
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68190 PLASTIC UNICHEM 7511B-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68104 PLASTIC UNICHEM 7512G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006321 4

Information Handling Services, 2000

68144 PLASTIC UNICHEM 7533
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68256 PLASTIC UNICHEM 7533A FR
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68046 PLASTIC UNICHEM 7575
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68058 PLASTIC UNICHEM 7580
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68255 PLASTIC UNICHEM 7588 CLEAR BLUE
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68187 PLASTIC UNICHEM 7712-G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68188 PLASTIC UNICHEM 7712F-NBBM
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68143 PLASTIC UNICHEM 7805
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68142 PLASTIC UNICHEM 7805 (CLEAR)
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68254 PLASTIC UNICHEM 7810
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68124 PLASTIC UNICHEM 7811
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68186 PLASTIC UNICHEM 7811-30
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68105 PLASTIC UNICHEM 7812G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68184 PLASTIC UNICHEM 7813
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006322 6 ■

Information Handling Services, 2000

68115 PLASTIC UNICHEM 7815
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68185 PLASTIC UNICHEM 7815G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68253 PLASTIC UNICHEM 7834
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68252 PLASTIC UNICHEM 7849
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68223 PLASTIC UNICHEM 7933H
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68222 PLASTIC UNICHEM 80-111K
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68035 PLASTIC UNICHEM 8000
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68251 PLASTIC UNICHEM 8000 FR-UV
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68250 PLASTIC UNICHEM 8000-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68075 PLASTIC UNICHEM 8005
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68141 PLASTIC UNICHEM 8005-90
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68076 PLASTIC UNICHEM 8005C
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68077 PLASTIC UNICHEM 8006 MG
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68125 PLASTIC UNICHEM 8011
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006323 8

Information Handling Services, 2000

68181 PLASTIC UNICHEM 8011 RADIO-OPAQUE
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68178 PLASTIC UNICHEM 8011-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68179 PLASTIC UNICHEM 8011A-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68176 PLASTIC UNICHEM 8011AG-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68180 PLASTIC UNICHEM 8011G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68177 PLASTIC UNICHEM 8011K-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68182 PLASTIC UNICHEM 8012
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68106 PLASTIC UNICHEM 8012G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68249 PLASTIC UNICHEM 8012N-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68051 PLASTIC UNICHEM 8033
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68248 PLASTIC UNICHEM 8034
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68078 PLASTIC UNICHEM 8060
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68059 PLASTIC UNICHEM 8080
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68060 PLASTIC UNICHEM 8083
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006324 T ■

Information Handling Services, 2000

68081 PLASTIC UNICHEM 8085
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68183 PLASTIC UNICHEM 8090
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68047 PLASTIC UNICHEM 8090C
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

84347 PLASTIC UNICHEM 8091
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68244 PLASTIC UNICHEM 8092
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68247 PLASTIC UNICHEM 8093 NATURAL
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

84348 PLASTIC UNICHEM 8099
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68032 PLASTIC UNICHEM 8180FR-1
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68082 PLASTIC UNICHEM 8190
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68031 PLASTIC UNICHEM 8190FR-1
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68294 PLASTIC UNICHEM 82-378D
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68240 PLASTIC UNICHEM 8200 FR WHITE
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68241 PLASTIC UNICHEM 8200FR
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68083 PLASTIC UNICHEM 8205
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006325 1

Information Handling Services, 2000

68243 PLASTIC UNICHEM 8299
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68126 PLASTIC UNICHEM 8311
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68175 PLASTIC UNICHEM 8311A
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68171 PLASTIC UNICHEM 8311A-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68172 PLASTIC UNICHEM 8312B-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68107 PLASTIC UNICHEM 8312G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68161 PLASTIC UNICHEM 84-209C
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68160 PLASTIC UNICHEM 84-369
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68159 PLASTIC UNICHEM 84-421D
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68292 PLASTIC UNICHEM 85-268F
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68036 PLASTIC UNICHEM 8500
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68127 PLASTIC UNICHEM 8511
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68242 PLASTIC UNICHEM 8511-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68173 PLASTIC UNICHEM 8511A-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006326 3

Information Handling Services, 2000

68108 PLASTIC UNICHEM 8512G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68174 PLASTIC UNICHEM 8512N-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68052 PLASTIC UNICHEM 8533
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68030 PLASTIC UNICHEM 8560
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68239 PLASTIC UNICHEM 8562
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68080 PLASTIC UNICHEM 8580
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68166 PLASTIC UNICHEM 8588
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68228 PLASTIC UNICHEM 8614
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68238 PLASTIC UNICHEM 8634
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68167 PLASTIC UNICHEM 8681
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68237 PLASTIC UNICHEM 8703
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68084 PLASTIC UNICHEM 8705
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68137 PLASTIC UNICHEM 8705-FR
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68168 PLASTIC UNICHEM 8711A-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006327 5

68029 PLASTIC UNICHEM 8715
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68236 PLASTIC UNICHEM 8733
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68048 PLASTIC UNICHEM 8804
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68245 PLASTIC UNICHEM 8901
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68138 PLASTIC UNICHEM 8990
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68037 PLASTIC UNICHEM 9000
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68165 PLASTIC UNICHEM 9001C-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68234 PLASTIC UNICHEM 9003
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68085 PLASTIC UNICHEM 9005
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68128 PLASTIC UNICHEM 9011
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68109 PLASTIC UNICHEM 9012G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68233 PLASTIC UNICHEM 9012H-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68053 PLASTIC UNICHEM 9033
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68232 PLASTIC UNICHEM 9034A-FRLS
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006328 7 ■

Information Handling Services, 2000

68266 PLASTIC UNICHEM 9090B
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68140 PLASTIC UNICHEM 9172C
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68231 PLASTIC UNICHEM 9314A
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68038 PLASTIC UNICHEM 9500
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68129 PLASTIC UNICHEM 9511
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68230 PLASTIC UNICHEM 9511A-02
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68110 PLASTIC UNICHEM 9512G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68229 PLASTIC UNICHEM 9554-F4
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68130 PLASTIC UNICHEM 9611
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68111 PLASTIC UNICHEM 9612G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68049 PLASTIC UNICHEM 9614
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68169 PLASTIC UNICHEM 9712A-02-HS
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68086 PLASTIC UNICHEM 9805
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68131 PLASTIC UNICHEM 9811
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006329 9

68112 PLASTIC UNICHEM 9811-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68164 PLASTIC UNICHEM 9811-15
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68113 PLASTIC UNICHEM 9812G-015
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68227 PLASTIC UNICHEM 9813
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68054 PLASTIC UNICHEM 9813 (BLACK,WHITE,BROWN)
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68295 PLASTIC UNICHEM 9813 (GREENS)
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68028 PLASTIC UNICHEM 9814
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68226 PLASTIC UNICHEM 9833
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68132 PLASTIC UNICHEM 9904
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68163 PLASTIC UNICHEM 9904-03
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68265 PLASTIC UNICHEM AA7093
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68225 PLASTIC UNICHEM AG8757E
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

68170 PLASTIC UNICHEM CUM8882
MANF: COLORITE PLASTICS CO
....NO TEST DATA AVAILABLE....

83792 PLASTIC USS C040Y
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006330 5

83793 PLASTIC USS C120Y
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83794 PLASTIC USS C432-12
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83795 PLASTIC USS C432-4
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83796 PLASTIC USS CP350A
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83797 PLASTIC USS CP450A
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83798 PLASTIC USS CR080A
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83799 PLASTIC USS CRVO-8
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83800 PLASTIC USS D007W
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83801 PLASTIC USS F007
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83802 PLASTIC USS F010M
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83803 PLASTIC USS F012
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83804 PLASTIC USS F012M
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83805 PLASTIC USS F015
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83806 PLASTIC USS F040F
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006331 7

Information Handling Services, 2000

83807 PLASTIC USS F080F
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83808 PLASTIC USS F080L
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83809 PLASTIC USS F1202L
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83810 PLASTIC USS F120F
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83811 PLASTIC USS F120L
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83812 PLASTIC USS FP120F
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83813 PLASTIC USS FP200F
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83814 PLASTIC USS FP300F
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83815 PLASTIC USS FP330W
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83816 PLASTIC USS FPT120F
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83817 PLASTIC USS FPT180F
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83818 PLASTIC USS FPT230F
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83819 PLASTIC USS FPT350F
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83820 PLASTIC USS FT040W
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006332 9 ■

83822 PLASTIC USS FT120C
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83823 PLASTIC USS FT120W
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83824 PLASTIC USS FT120W2L
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83825 PLASTIC USS FT120WB
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83826 PLASTIC USS FT145V
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83827 PLASTIC USS L040G
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83828 PLASTIC USS T14025G
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83829 PLASTIC USS T14040G
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83830 PLASTIC USS T14070G
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83831 PLASTIC USS T14230G
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83832 PLASTIC USS T15035G
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83833 PLASTIC USS T15230G
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

83821 PLASTIC USSS FT080W
MANF: U S STEEL
....NO TEST DATA AVAILABLE....

05541 PLASTIC VALOX 310 SEO POLYESTER

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.32	.05	.00	

ODOR		TOXICITY
RT	RT WEIGHT	CURE
No test data		

MSFC-HDBK-527 REV F 9999942 0006333 0

69465 PLASTIC VALOX 325
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81805 PLASTIC VALOX 357
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69466 PLASTIC VALOX 365
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69468 PLASTIC VALOX 414 40% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69476 PLASTIC VALOX 420 30% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

05250 PLASTIC VALOX 420 SEO POLYESTER/GLASS GID: DKCBIA
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.256		00.05	12.00 T	MOD
A	1	023.8	014.5	0.050			02.40	NONE
A	1	025.9	014.3	0.500		00.16	01.30	NONE
X	1	030.0	009.0	0.256		00.04	12.20 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.35	.07		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.22	

69477 PLASTIC VALOX 430 30% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69478 PLASTIC VALOX 508 30% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69469 PLASTIC VALOX 553 30% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69470 PLASTIC VALOX 701 35% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81806 PLASTIC VALOX 730
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

62265 PLASTIC VALOX 730-1001 POLYESTER GID: DKCBXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.102			01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006334 2

62265 PLASTIC VALOX 730-1001 POLYESTER (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.102		00.07	06.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00226.55	

69479 PLASTIC VALOX 735 40% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81807 PLASTIC VALOX 736
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69483 PLASTIC VALOX 740 30% MINERAL
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69471 PLASTIC VALOX 752 45% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69484 PLASTIC VALOX 760 25% MINERAL
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69472 PLASTIC VALOX 780 40% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69480 PLASTIC VALOX 815 15% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69473 PLASTIC VALOX 830 30% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69481 PLASTIC VALOX 850 15% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69474 PLASTIC VALOX 855 15% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69482 PLASTIC VALOX 865 30% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69467 PLASTIC VALOX DR-48 15% GLASS
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.72	.41	.00	

ODOR

RT

No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006335 4

69475 PLASTIC VALOX DR-51 15% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

83980 PLASTIC VB511
MANF: WASHINGTON PENN PLASTICS
....NO TEST DATA AVAILABLE....

81669 PLASTIC VE49595
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

84026 PLASTIC VERTON RF-700-10
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84027 PLASTIC VERTON RF-700-1EM
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84028 PLASTIC VERTON RF-7003FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84029 PLASTIC VERTON RF-7006
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84030 PLASTIC VERTON RF-7006EM
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84031 PLASTIC VERTON RF-7006FR
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84876 PLASTIC VESTODUR 1000
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84879 PLASTIC VESTODUR 2000
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84881 PLASTIC VESTODUR 2000 SO
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84884 PLASTIC VESTODUR 3000
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84887 PLASTIC VESTODUR GK 30
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006336 6

Information Handling Services, 2000

84889 PLASTIC VESTODUR MGF 30
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84893 PLASTIC VESTODUR MIN 125
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84895 PLASTIC VESTODUR SGF 15
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84899 PLASTIC VESTODUR SGF 20
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84902 PLASTIC VESTODUR SGF 20 SO
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84904 PLASTIC VESTODUR SGF 30
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84907 PLASTIC VESTODUR SGF 30 SO
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84913 PLASTIC VESTODUR SGF 50
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

82381 PLASTIC VICTREX PEEK
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

80070 PLASTIC VICTREX PEEK 25% GLASS-FILLED
MANF: FLUOROCARBON CORP

FLAMMABILITY								FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		C	MECH	300	45	150	0.060	0	20

84032 PLASTIC VICTREX PEEK 450CA30
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84033 PLASTIC VICTREX PEEK 450G
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84034 PLASTIC VICTREX PEEK 450GL30
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84035 PLASTIC VICTREX PEEK D150CA30
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006337 8

84036 PLASTIC VICTREX PEEK D150GL30
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84037 PLASTIC VICTREX PES 4100G
MANF: ICI ADVANCED
L N P CORP

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.090		00.05	01.50	NONE	No test data		No test data							
A	1	030.0	010.2	0.090		00.03	02.00	NONE										

84038 PLASTIC VICTREX PES 4101GL20
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84039 PLASTIC VICTREX PES 410GL30
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84040 PLASTIC VICTREX PES D4800HF30
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

84041 PLASTIC VICTREX PES D4800HL15
MANF: L N P CORP
....NO TEST DATA AVAILABLE....

80993 PLASTIC VINIDUR SZ6415
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80994 PLASTIC VINIDUR SZ6415/VINOFLEX S6815
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80995 PLASTIC VINOFLEX S6115
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

80996 PLASTIC VINOFLEX S6815
MANF: BASF STRUCTURAL MATERIALS
....NO TEST DATA AVAILABLE....

69494 PLASTIC VITUF 6204
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

69495 PLASTIC VITUF 6209
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

69496 PLASTIC VITUF 7002
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006338 T ■

69497 PLASTIC VITUF 7800G
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

69498 PLASTIC VITUF 9505
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

80538 PLASTIC VIVAK SHEET
MANF: AEROMAT PLASTICS
....NO TEST DATA AVAILABLE....

80545 PLASTIC VIXTRIX 450 CA30
MANF: AFTON PLASTICS
....NO TEST DATA AVAILABLE....

80546 PLASTIC VIXTRIX 450G
MANF: AFTON PLASTICS
....NO TEST DATA AVAILABLE....

80547 PLASTIC VIXTRIX 450GL30
MANF: AFTON PLASTICS
....NO TEST DATA AVAILABLE....

80548 PLASTIC VIXTRIX D150CA30
MANF: AFTON PLASTICS
....NO TEST DATA AVAILABLE....

80549 PLASTIC VIXTRIX D150G
MANF: AFTON PLASTICS
....NO TEST DATA AVAILABLE....

80550 PLASTIC VIXTRIX D150GL30
MANF: AFTON PLASTICS
....NO TEST DATA AVAILABLE....

80777 PLASTIC VPC TYPE 2
MANF: ATOCHEM
....NO TEST DATA AVAILABLE....

69502 PLASTIC VPE-4583A
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

69507 PLASTIC VPE-4670A
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

69509 PLASTIC VPE-5253
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

69510 PLASTIC VPE-5833A
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006339 1

69511 PLASTIC VPE-5987A
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

69508 PLASTIC VPE5066A
MANF: GOODYEAR
....NO TEST DATA AVAILABLE....

84659 PLASTIC VYDYNE 21
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84662 PLASTIC VYDYNE 21SP
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84664 PLASTIC VYDYNE 21X
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84666 PLASTIC VYDYNE 22H
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84668 PLASTIC VYDYNE 22HSP
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84672 PLASTIC VYDYNE 24HSP
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84675 PLASTIC VYDYNE 25W
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84677 PLASTIC VYDYNE 60H
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84679 PLASTIC VYDYNE 65B
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84682 PLASTIC VYDYNE 66B
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84684 PLASTIC VYDYNE 909
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84686 PLASTIC VYDYNE M340
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006340 8 ■

Information Handling Services, 2000

84691 PLASTIC VYDYNE M344
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84693 PLASTIC VYDYNE M345
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84696 PLASTIC VYDYNE R-100
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84697 PLASTIC VYDYNE R-200
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84699 PLASTIC VYDYNE R-220
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84701 PLASTIC VYDYNE R-250
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84708 PLASTIC VYDYNE R-400
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84710 PLASTIC VYDYNE R-513
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84712 PLASTIC VYDYNE R-513H
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84713 PLASTIC VYDYNE R-533
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84731 PLASTIC VYDYNE R-533H
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84732 PLASTIC VYDYNE R-538H-02
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84733 PLASTIC VYDYNE R-543
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

84734 PLASTIC VYDYNE R-543H
MANF: MONSANTO
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006341 T ■

Information Handling Services, 2000

69751 PLASTIC WEAR RESISTANT LIQUID
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

69750 PLASTIC WEAR RESISTANT PUTTY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

83981 PLASTIC WELLAMID 210N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

83982 PLASTIC WELLAMID 21L-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

83983 PLASTIC WELLAMID 21LH-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

83984 PLASTIC WELLAMID 21LN2-NNT
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

83985 PLASTIC WELLAMID 21U-NBK1
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

83986 PLASTIC WELLAMID 220N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

83987 PLASTIC WELLAMID 22L-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

83988 PLASTIC WELLAMID 22LH-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

83989 PLASTIC WELLAMID 22LH13XE-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

83990 PLASTIC WELLAMID 22LH14XE-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

83991 PLASTIC WELLAMID 22LH15XE-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

83993 PLASTIC WELLAMID 22LN2-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006342 1 ■

83992 PLASTIC WELLAMID 33LH16XE-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

83994 PLASTIC WELLAMID 420N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

83995 PLASTIC WELLAMID 420XE-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81918 PLASTIC WELLAMID 42HI11-XE-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

83996 PLASTIC WELLAMID 42L-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

83997 PLASTIC WELLAMID 42L-XE-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81913 PLASTIC WELLAMID 42LH-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81916 PLASTIC WELLAMID 42LH-XE-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81920 PLASTIC WELLAMID 42LH-2-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81922 PLASTIC WELLAMID 42LH-2-XE-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81923 PLASTIC WELLAMID FR22F-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81924 PLASTIC WELLAMID FR64-NRD
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81925 PLASTIC WELLAMID FRGF25-66-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81926 PLASTIC WELLAMID FRGS25-66-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

81928 PLASTIC WELLAMID GF13-60-42LH-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81933 PLASTIC WELLAMID GF13-66 X3-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81930 PLASTIC WELLAMID GF13-66-22LH-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81935 PLASTIC WELLAMID GF30-60 42LH-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81936 PLASTIC WELLAMID GF30-60 XE-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81939 PLASTIC WELLAMID GF33-66 22LH-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81941 PLASTIC WELLAMID GF33-66 XE-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81943 PLASTIC WELLAMID GF33-66 XE-N1
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81947 PLASTIC WELLAMID GFT13-66 XE-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81945 PLASTIC WELLAMID GR43-66 XE-N1
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81949 PLASTIC WELLAMID GS25-66 22L-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81951 PLASTIC WELLAMID GS25-66 LH-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81959 PLASTIC WELLAMID GS40-60 22L-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81953 PLASTIC WELLAMID GS40-60 42L-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006344 5 ■

81957 PLASTIC WELLAMID GS40-60 42LH-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81961 PLASTIC WELLAMID GSF25/15-66 22L-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81965 PLASTIC WELLAMID MR259 22LH-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81962 PLASTIC WELLAMID MR409 22H-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81971 PLASTIC WELLAMID MR410 22H-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81974 PLASTIC WELLAMID MRGF25/15 22H-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81976 PLASTIC WELLAMID MRGF25/15 42H-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

81978 PLASTIC WELLAMID MRGF30/10 42H-N
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

82383 PLASTIC WESTLAKE CELCON/25PCT GLASS
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82382 PLASTIC WESTLAKE CELCON/UNFILLED
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82384 PLASTIC WESTLAKE ETHYLUX
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82385 PLASTIC WESTLAKE LENNITE
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82386 PLASTIC WESTLAKE LENNITE UHMW
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82387 PLASTIC WESTLAKE LENNITE XL
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006345 7

82388 PLASTIC WESTLAKE NORYL EN-185
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82389 PLASTIC WESTLAKE NORYL SE-1-GFN3
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82390 PLASTIC WESTLAKE POLYMETHYLPENTENE
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82391 PLASTIC WESTLAKE POLYSTYRENE
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82393 PLASTIC WESTLAKE PROPYLUX
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82395 PLASTIC WESTLAKE STYROLUX
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82397 PLASTIC WESTLAKE VICTREX
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82400 PLASTIC WESTLAKE VICTREX 4101GL30 (30 PCT REINFORCED)
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82402 PLASTIC WESTLAKE ZELUX
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82405 PLASTIC WESTLAKE ZELUX 10 PCT GLASS REINFORCED
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82406 PLASTIC WESTLAKE ZELUX 20 PCT GLASS REINFORCED
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82408 PLASTIC WESTLAKE ZELUX 40 PCT GLASS REINFORCED
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

82409 PLASTIC WESTLAKE ZELUX W
MANF: WESTLAKE PLASTICS CO
....NO TEST DATA AVAILABLE....

69758 PLASTIC WET SURFACE REPAIR PUTTY
MANF: DEVCON CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F ■ 9999942 0006346 9 ■

Information Handling Services, 2000

81670 PLASTIC X28057
MANF: FIBERITE
....NO TEST DATA AVAILABLE....

69412 PLASTIC XENOY 2230
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69413 PLASTIC XENOY 3220
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69414 PLASTIC XENOY 3221
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69419 PLASTIC XENOY 3225
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69411 PLASTIC XENOY 5220
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69415 PLASTIC XENOY 6120
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69420 PLASTIC XENOY 6121
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69416 PLASTIC XENOY 6123
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69417 PLASTIC XENOY 6240 10% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69422 PLASTIC XENOY 6370 30% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69418 PLASTIC XENOY 6380 30% GLASS
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

69421 PLASTIC XENOY 6620
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

68871 PLASTIC XO-712
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006347 0

68873 PLASTIC XO-719
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68872 PLASTIC XO-754
MANF: EL PASO PRODUCTS
....NO TEST DATA AVAILABLE....

68917 PLASTIC XQ-32
MANF: EXXON
....NO TEST DATA AVAILABLE....

68918 PLASTIC XQ-36
MANF: EXXON
....NO TEST DATA AVAILABLE....

68919 PLASTIC XQ-43
MANF: EXXON
....NO TEST DATA AVAILABLE....

68920 PLASTIC XQ-46
MANF: EXXON
....NO TEST DATA AVAILABLE....

83597 PLASTIC XYLON/VO NYLON UNREINFORCED
MANF: WILSON FIBERFIL
....NO TEST DATA AVAILABLE....

80267 PLASTIC YELLOW VINYL CAPS FORMULA 701 GID: DKXXXX
MANF: GFE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.035		00.09	12.60	T SMALL
X	1	030.0	010.0	0.035		0.4	12.60	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	10.984	

81360 PLASTIC YUKALON AH-40
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81361 PLASTIC YUKALON EC-51B
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81362 PLASTIC YUKALON EC-70
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81363 PLASTIC YUKALON EH-30
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81364 PLASTIC YUKALON HK-30
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006348 2

81365 PLASTIC YUKALON HE-40
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81366 PLASTIC YUKALON HE-60
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81367 PLASTIC YUKALON LK-30
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81377 PLASTIC YUKALON LK-50
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81378 PLASTIC YUKALON LM-30
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81380 PLASTIC YUKALON LM-31
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81382 PLASTIC YUKALON LM-40
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81383 PLASTIC YUKALON LS-30
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81384 PLASTIC YUKALON MS-30
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81385 PLASTIC YUKALON MT-30
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81386 PLASTIC YUKALON MV-30
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81387 PLASTIC YUKALON NF40
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81388 PLASTIC YUKALON NH-50
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81390 PLASTIC YUKALON YF-30
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006349 4

Information Handling Services, 2000

81391 PLASTIC YUKALON YK-30
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81393 PLASTIC YUKALON YK-50
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81394 PLASTIC YUKALON YK-60
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81396 PLASTIC YUKALON YM-61
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81397 PLASTIC YUKALON ZC-30
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81398 PLASTIC YUKALON ZC-52
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81401 PLASTIC YUKALON ZE-41
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81403 PLASTIC YUKALON ZE-61
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81404 PLASTIC YUKALON ZF-30
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81407 PLASTIC YUKALON ZF-50
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81408 PLASTIC YUKALON ZF-51
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81409 PLASTIC YUKALON ZF-52
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

81411 PLASTIC YUKALON ZF-53
MANF: MITSUBISHI
....NO TEST DATA AVAILABLE....

69807 PLASTIC ZELUX M131 GID: DKXXXX
MANF: WESTLAKE PLASTICS CO

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	001001.1	

MSFC-HDBK-527 REV F 9999942 0006350 0

Information Handling Services, 2000

80744 PLASTIC ZONAREZ 7115
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80745 PLASTIC ZONAREZ 7115 LITE
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80746 PLASTIC ZONAREZ 7125
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80747 PLASTIC ZONAREZ 7125 LITE
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80748 PLASTIC ZONAREZ ALPHA 25
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80750 PLASTIC ZONAREZ B-125
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80751 PLASTIC ZONAREZ M115
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80749 PLASTIC ZONAREZA B-115
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80752 PLASTIC ZONATAC 105
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80753 PLASTIC ZONATAC 105 LITE
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80754 PLASTIC ZONATAC 115 LITE
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80755 PLASTIC ZONATAC 501
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80756 PLASTIC ZONATAC 501 LITE
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80757 PLASTIC ZONESTER 100
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006351 2

80758 PLASTIC ZONESTER 55
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80759 PLASTIC ZONESTER 65
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80760 PLASTIC ZONESTER 75
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

80761 PLASTIC ZONESTER 85
MANF: ARIZONA CHEMICAL
....NO TEST DATA AVAILABLE....

68629 PLASTIC ZYTEL 101
MANF: DUPONT

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.09	.03	.00		No test data		

68631 PLASTIC ZYTEL 101L
MANF: DUPONT

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.31	.03	.00		No test data		

68632 PLASTIC ZYTEL 105
MANF: DUPONT
....NO TEST DATA AVAILABLE....

85205 PLASTIC ZYTEL 109L
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68633 PLASTIC ZYTEL 133C
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68635 PLASTIC ZYTEL 158C
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68640 PLASTIC ZYTEL 211
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68638 PLASTIC ZYTEL 408
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68639 PLASTIC ZYTEL 408 HS
MANF: DUPONT
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006352 4 ■

68634 PLASTIC ZYTEL 408C
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68630 PLASTIC ZYTEL 42
MANF: DUPONT

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.57	.26	.00		No test data		

68636 PLASTIC ZYTEL 91 HS
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68641 PLASTIC ZYTEL ST 801
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68637 PLASTIC ZYTEL ST 811
MANF: DUPONT
....NO TEST DATA AVAILABLE....

68642 PLASTIC ZYTEL ST 811 HS
MANF: DUPONT
....NO TEST DATA AVAILABLE....

80592 PLASTICS ARNITEL 63D G1-G6
MANF: AKZO PLASTICS
....NO TEST DATA AVAILABLE....

82337 PLASTICS RESINOID 2010
MANF: RESINOID ENGINEERING
....NO TEST DATA AVAILABLE....

82371 PLASTICS WELLITE 9000GP
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

82372 PLASTICS WELLITE 9320GR
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

82373 PLASTICS WELLITE 9330GR
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

82374 PLASTICS WELLITE 9730GRVO
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

82376 PLASTICS WELLPET FG1020
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

82375 PLASTICS WELLPET FRGF2030
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006353 6

82377 PLASTICS WELLPET GF1030
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

82378 PLASTICS WELLPET GF1045
MANF: WELLMAN INC
....NO TEST DATA AVAILABLE....

06470 PLATE ID TEMPILABLE 8D-XXX/XXX
....NO TEST DATA AVAILABLE....

20041 PLATE TERMINAL POLYESTER GID: FPCBXX
MANF: AQM
....NO TEST DATA AVAILABLE....

63786 PLATES LEAD GID: FCMPXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	27240.00	

63972 PLATING GOLD ON A-286
MANF: ROCKETDYNE
SPEC: AMS 5525

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	MECH	4800	368	543	0.001	0	20

61792 PNEUMATIC SURGE TEST FIXTURE GID: FEXXXX
MANF: CARLETON CONTROLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70		0	20
B	PNEU	6000		70		0	40

60422 POLY (AMIDE-IMIDE)
MANF:
SPEC: RB0130-089

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.54	.00	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

06308 POLYCARBONATE AMBER 1663
....NO TEST DATA AVAILABLE....

80197 POLYCARBONATE PANLITE L1250 GID: DDXXXX
MANF: TEIJIN-KASEI CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.060		00.09	12.00	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	22.783	

80195 POLYCARBONATE TAKIRON PANLITE PLATE GID: DDXXXX
MANF: TAKIRON CHEMICAL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.040		00.09	12.00	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	21.745	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006354 8

60691 POLYCAST RG256-57-3 GID: DMCQGS

MANF: UPJOHN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-7	1.52	.01		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60149 POLYETHYLENE

MANF: AQM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.02	.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60434 POLYIMIDE-CU

MANF: SPEC: MC8017-01

....NO TEST DATA AVAILABLE....

60303 POLYOLEFIN HS COMPONENTS

MANF: SPEC: MIL-I-81765/1

....NO TEST DATA AVAILABLE....

63293 POLYPHENYL ETHER 4 AND 5 RING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
V	00005.00	

TOXICITY

20371 POLYPROPYLENE STYLE 9079 GID: DLCGXX

MANF: FABLOCK MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.043			06.50	SMALL
X	2	025.9	014.3	0.035		00.20	12.00	T MOD
X	1	025.9	014.3	0.035		00.55	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.2E-7	1.06	.58		

ODOR

RT	RT WEIGHT	CURE
A	00016.65	

TOXICITY

63920 POLYSTYRENE PETRI DISH

MANF: FISHER SCIENTIFIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00015.98	

TOXICITY

60418 POLYURETHANE

....NO TEST DATA AVAILABLE....

63195 POREFLON P/N FP080 PTFE GID: DTCOXX

MANF: SUMITOMO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.003		01.14	03.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00004.13	

TOXICITY

60703 POTENTIOMETER TYS GID: EZXXXX

MANF: ALLEN-BRADLEY CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	1.500		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006355 T

60703 POTENTIOMETER TYS (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00051.75	

TOXICITY

05572 POTTING COMPOUND IMPCO RC2 POLYESTER GID: BACBXX

MANF: METALPLAST INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	V	00003.78	1H-275F-

TOXICITY

60771 POTTING COMPOUND 93-500/ALUMINUM-OXIDE FILL GID: BAFKXX

MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.7E-6	.12	.04	.01	168H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60770 POTTING COMPOUND 93-500/CU MICROSPHER GID: BAHNXX

MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.7E-6	.12	.01	.01	168H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05815 POTTING COMPOUND ABLECAST 402 GID: BABGXX

MANF: ABLESTIK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.009	0.003	00.00	00.00	NONE
X	1	023.8	014.5	0.009	0.003	00.84	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.2E-7	5.40	.29		2H-165F-

ODOR

RT	RT	WEIGHT	CURE
	X	00022.01	2H-165F-

TOXICITY

60117 POTTING COMPOUND ARCOSET 200 EPOXY GID: BABGXX

MANF: ARCAL CHEMICALS

....NO TEST DATA AVAILABLE....

05672 POTTING COMPOUND BERLON E0383 GID: BAXXXX

MANF: NATIONAL BERYLLIA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.018	0.003		05.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05674 POTTING COMPOUND BERLON E33 GID: BAXXXX

MANF: NATIONAL BERYLLIA

....NO TEST DATA AVAILABLE....

05830 POTTING COMPOUND C9-4210/H2-3561/2775 GID: BABGXX

MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.107		00.02	12.00	T MOD
X	1	023.8	014.5	0.107		00.64	12.10	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	1.74	.77		96H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00050.44	96H-70F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006356 1

20168 POTTING COMPOUND C9W690/HD3615 GID: BABGXX

MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.015	0.003		03.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00026.36	2H-302F-

62272 POTTING COMPOUND CASTALL 301/RT1 GID: BABGXX

MANF: CASTALL INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.010	0.003	00.00	00.00	NONE
A	1	020.9	014.7	0.010	0.003		06.20	NONE
C	1	030.0	009.0	0.010	0.003		07.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	8.0E-6	.74	.02		24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00023.24	24H-70F-

61183 POTTING COMPOUND CASTALL A301/E34 GID: BABGXX

MANF: CASTALL INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.29	.00		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05218 POTTING COMPOUND CB1054 A/B EPOXY GID: BABGXX

MANF: JOHN C DOLPH CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.018		00.00	00.00	NONE
A	1	023.8	014.5	0.018			01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	6.0E-7	3.03	1.93		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00021.55	10H-225F-

84268 POTTING COMPOUND CONATHANE DPEN8536

MANF: CONAP

....NO TEST DATA AVAILABLE....

84269 POTTING COMPOUND CONATHANE EN10

MANF: CONAP

....NO TEST DATA AVAILABLE....

84270 POTTING COMPOUND CONATHANE EN11

MANF: CONAP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.27	.01	.00	10H-140F-
					24H-140F-0psiaVACUUM

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	20.7	

84271 POTTING COMPOUND CONATHANE EN12

MANF: CONAP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.43	.01	.00	48H-122F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006357 3

84273 POTTING COMPOUND CONATHANE EN20
MANF: CONAP
....NO TEST DATA AVAILABLE....

84274 POTTING COMPOUND CONATHANE EN21
MANF: CONAP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.50	.03	.00	336H-70F-	No test data		

84303 POTTING COMPOUND CONATHANE EN22
MANF: CONAP
....NO TEST DATA AVAILABLE....

84294 POTTING COMPOUND CONATHANE EN23
MANF: CONAP
....NO TEST DATA AVAILABLE....

84295 POTTING COMPOUND CONATHANE EN24
MANF: CONAP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.57	.04	.00	168H-70F-	No test data		

84275 POTTING COMPOUND CONATHANE EN2523
MANF: CONAP
....NO TEST DATA AVAILABLE....

84276 POTTING COMPOUND CONATHANE EN2524
MANF: CONAP
....NO TEST DATA AVAILABLE....

84277 POTTING COMPOUND CONATHANE EN2525
MANF: CONAP
....NO TEST DATA AVAILABLE....

84278 POTTING COMPOUND CONATHANE EN2526
MANF: CONAP
....NO TEST DATA AVAILABLE....

84279 POTTING COMPOUND CONATHANE EN2527
MANF: CONAP
....NO TEST DATA AVAILABLE....

84280 POTTING COMPOUND CONATHANE EN2528
MANF: CONAP
....NO TEST DATA AVAILABLE....

84304 POTTING COMPOUND CONATHANE EN2541
MANF: CONAP
....NO TEST DATA AVAILABLE....

84305 POTTING COMPOUND CONATHANE EN2543
MANF: CONAP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006358 5 ■

84306 POTTING COMPOUND CONATHANE EN2545
MANF: CONAP
....NO TEST DATA AVAILABLE....

84307 POTTING COMPOUND CONATHANE EN2547
MANF: CONAP
....NO TEST DATA AVAILABLE....

84308 POTTING COMPOUND CONATHANE EN2548
MANF: CONAP
....NO TEST DATA AVAILABLE....

84296 POTTING COMPOUND CONATHANE EN30
MANF: CONAP
....NO TEST DATA AVAILABLE....

84282 POTTING COMPOUND CONATHANE EN5
MANF: CONAP

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.78	.02	.00	168H-70F-

ODOR		TOXICITY
RT	RT WEIGHT	CURE
No test data		

84283 POTTING COMPOUND CONATHANE EN6
MANF: CONAP

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.76	.01	.44	8H-230F-

ODOR		TOXICITY
RT	RT WEIGHT	CURE
No test data		

84284 POTTING COMPOUND CONATHANE EN7
MANF: CONAP

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.32	.01	.00	20H-70F- 24H-140F-

ODOR		TOXICITY
RT	RT WEIGHT	CURE
No test data		

84285 POTTING COMPOUND CONATHANE EN8
MANF: CONAP
....NO TEST DATA AVAILABLE....

84286 POTTING COMPOUND CONATHANE EN9
MANF: CONAP

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.44	.00	.00	.5H-46F- 8H-199F-

ODOR		TOXICITY
RT	RT WEIGHT	CURE
No test data		

84287 POTTING COMPOUND CONATHANE EN9 (OZR)
MANF: CONAP
....NO TEST DATA AVAILABLE....

84309 POTTING COMPOUND CONATHANE TU400
MANF: CONAP
....NO TEST DATA AVAILABLE....

84297 POTTING COMPOUND CONATHANE TU4010
MANF: CONAP
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006359 7

84310 POTTING COMPOUND CONATHANE TU500
MANF: CONAP
....NO TEST DATA AVAILABLE....

84311 POTTING COMPOUND CONATHANE TU50A
MANF: CONAP
....NO TEST DATA AVAILABLE....

84312 POTTING COMPOUND CONATHANE TU600
MANF: CONAP
....NO TEST DATA AVAILABLE....

84313 POTTING COMPOUND CONATHANE TU65A
MANF: CONAP
....NO TEST DATA AVAILABLE....

84314 POTTING COMPOUND CONATHANE TU700
MANF: CONAP
....NO TEST DATA AVAILABLE....

84315 POTTING COMPOUND CONATHANE TU79
MANF: CONAP
....NO TEST DATA AVAILABLE....

84316 POTTING COMPOUND CONATHANE TU80
MANF: CONAP
....NO TEST DATA AVAILABLE....

84317 POTTING COMPOUND CONATHANE TU800
MANF: CONAP
....NO TEST DATA AVAILABLE....

84318 POTTING COMPOUND CONATHANE TU89
MANF: CONAP
....NO TEST DATA AVAILABLE....

84319 POTTING COMPOUND CONATHANE TU900
MANF: CONAP
....NO TEST DATA AVAILABLE....

84320 POTTING COMPOUND CONATHANE TU955
MANF: CONAP
....NO TEST DATA AVAILABLE....

84267 POTTING COMPOUND CONATHANE TU960
MANF: CONAP
....NO TEST DATA AVAILABLE....

84288 POTTING COMPOUND CONATHANE UC17
MANF: CONAP
....NO TEST DATA AVAILABLE....

84321 POTTING COMPOUND CONATHANE UC21
MANF: CONAP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006360 3

Information Handling Services, 2000

84322 POTTING COMPOUND CONATHANE UC22
MANF: CONAP
....NO TEST DATA AVAILABLE....

84323 POTTING COMPOUND CONATHANE UC23
MANF: CONAP
....NO TEST DATA AVAILABLE....

84324 POTTING COMPOUND CONATHANE UC24
MANF: CONAP
....NO TEST DATA AVAILABLE....

84325 POTTING COMPOUND CONATHANE UC25
MANF: CONAP
....NO TEST DATA AVAILABLE....

84326 POTTING COMPOUND CONATHANE UC26
MANF: CONAP
....NO TEST DATA AVAILABLE....

84327 POTTING COMPOUND CONATHANE UC27
MANF: CONAP
....NO TEST DATA AVAILABLE....

84289 POTTING COMPOUND CONATHANE UC30
MANF: CONAP
....NO TEST DATA AVAILABLE....

84290 POTTING COMPOUND CONATHANE UC31
MANF: CONAP
....NO TEST DATA AVAILABLE....

84291 POTTING COMPOUND CONATHANE UC32
MANF: CONAP
....NO TEST DATA AVAILABLE....

84292 POTTING COMPOUND CONATHANE UC33
MANF: CONAP
....NO TEST DATA AVAILABLE....

84293 POTTING COMPOUND CONATHANE UC34
MANF: CONAP
....NO TEST DATA AVAILABLE....

84328 POTTING COMPOUND CONATHANE UF3
MANF: CONAP
....NO TEST DATA AVAILABLE....

05553 POTTING COMPOUND COX 28 EPOXY GID: BACKXX
MANF: COX & CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.024	0.003	00.00	00.00	NONE
C	1	023.8	014.5	0.024	0.003	00.17	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.75	1.61	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00067.58	16H-165F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006361 5

06139 POTTING COMPOUND COX 4021/4036 GID: EGCKXX
MANF: COX & CO
....NO TEST DATA AVAILABLE....

60342 POTTING COMPOUND DC183 GID: BAXXXX
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85495 POTTING COMPOUND DC4040 FLUOROSILICONE
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

60344 POTTING COMPOUND DC7521 SILICONE GID: BACKXX
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	2.62	1.34	.00	1.5H-248F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63008 POTTING COMPOUND DOLPHS CB1078/HARDNER GID: BAXXXX
MANF: LOCKHEED

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.5	0.350			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.34	.01	.00	168H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05260 POTTING COMPOUND E9405 EPOXY/GLASS GID: BABGIA
MANF: FIBERITE SPEC: MIL-M-14F

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.059		00.11	11.90	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	1500	72	69	0.065	2	02
X	MECH	1500	72	69	0.065	2	2
B	PNEU	1500		70	0.065	0	20
B	PNEU	1500		70	0.065	2	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	8.9E-6	.51	.01		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.03	

TOXICITY

60244 POTTING COMPOUND EA919 UF3280 CORK GID: BAXXXX
MANF: SPEC: STW5-2975
....NO TEST DATA AVAILABLE....

60203 POTTING COMPOUND EA937 GID: BAXXXX
MANF: SPEC: STW5 2930 T2
....NO TEST DATA AVAILABLE....

84329 POTTING COMPOUND EASYPOXY K230
MANF: CONAP
....NO TEST DATA AVAILABLE....

60769 POTTING COMPOUND ECN1235/ALUMINUM-OXIDE F GID: BAFKXX
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.7E-6	.14	.00	.09	17H-185F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006362 7

20167 POTTING COMPOUND EE0004/HD3561 GID: BAXXXX

MANF: HYSOL/DEXTER
P0524/P1208

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005	0.003		04.35	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	B 00016.15	2H-140F-

64187 POTTING COMPOUND EE4215/HD3615 GID: BABGXX

MANF: HYSOL/DEXTER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.060			00.20	NONE
C	1	030.0	010.0	0.060		00.40	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.2E-6	4.21	2.88	.07	2H-176F- 2H-300F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

05695 POTTING COMPOUND EPIREZ 5071/EPI841 GID: BAXXXX

....NO TEST DATA AVAILABLE....

64205 POTTING COMPOUND EPON 828/ALUMINUM/TONOX GID: BAFKXX

MANF: SHELL CHEMICAL
UNIROYAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.020		00.00	00.00	NONE
C	1	025.9	014.3	0.020		00.2	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	B 00021.92	3H-170F-

60978 POTTING COMPOUND EPOXY 0-73027-1 GID: BABGXX

MANF: GENERAL DYNAMICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.2E-6	2.22	.20	.23	1.42H-70F- 5H-150F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

65192 POTTING COMPOUND EPOXY AP1371 A/B GID: BABGXX

MANF: ADVANCED POLYMER IND SPEC: GD 65-00214-1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.090			00.10	SMALL
C	1	020.9	014.7	0.090		00.40	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	12.22	.55	.08	24H-70F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

05592 POTTING COMPOUND EPOXY C9-4215 GID: BABGXX

....NO TEST DATA AVAILABLE....

05565 POTTING COMPOUND EPOXY EC1469 GID: BABGXX

MANF: 3M CO

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006363 9

05565 POTTING COMPOUND EPOXY EC1469 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	A	00019.96	

62040 POTTING COMPOUND EPOXY PUTTY 3249 A/B GID: BABGGS

MANF: BROOKSTONE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.012	0.003	00.67	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	B	00017.60	24H-70F-
			24H-150F-

61861 POTTING COMPOUND EPOXY/SILICATE ES180 GID: BABGGP

MANF: POLY SCIENTIFIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.218		00.05	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61860 POTTING COMPOUND EPOXY/SILICATE ES218 GID: BABGGP

MANF: POLY SCIENTIFIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.132		00.04	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06120 POTTING COMPOUND EPOXYLITE 210/C321 GID: CADEXX

MANF: EPOXYLITE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.114			00.80	NONE
X	1	025.9	014.3	0.114		00.18	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	1.10	.19		24H-70F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	B	00019.93	24H-70F-

05929 POTTING COMPOUND FM1132 PHENOLIC GID: BABXXX

MANF: FIBERITE SPEC: MIL-M-14CFI-10

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.700			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.6E-7	4.30	.02		

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	V	00020.21	

80041 POTTING COMPOUND KE45 SILICONE GID: BACKXX

MANF: SHIN-ETSU CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.290	0.300		01.90	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT.	RT	WEIGHT	CURE
	X	21.846	16H-70F-
			216H-70F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006364 0

65180 POTTING COMPOUND NYLON BOOT GID: BABSXX

MANF: FEDERAL SUPPLY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	2.57	.03	.76	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61048 POTTING COMPOUND POLYURETHANE DC902-1 GID: BACQXX

MANF: DOW CORNING
REN PLASTICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.2E-6	12.24	.29		16H-176F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06109 POTTING COMPOUND POLYURETHANE PRP1538 GID: BACQXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.047			00.30	NONE
A	1	023.8	014.5	0.047			06.40	SMALL
X	1	030.0	009.0	0.020			05.10	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	14.7	72	-297	0.047	02	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.52	.05	.00	144H-140F-

ODOR

RT	RT WEIGHT	CURE
A	B 00019.68	24H-70F-
		24H-130F-

TOXICITY

64264 POTTING COMPOUND PR1201Q GID: BAXXXX

MANF: RESEARCH CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.140		00.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	36.32	2.78	.00	72H-77F-

ODOR

RT	RT WEIGHT	CURE
	X 00111.33	

TOXICITY

05935 POTTING COMPOUND PR1547 BLACK POLYURETHANE GID: BACQXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7				02.20	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.72	.03		24H-70F-

ODOR

RT	RT WEIGHT	CURE
	A 00091.72	

TOXICITY

06269 POTTING COMPOUND PR1578 POLYURETHANE GID: BACQXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.069			02.30	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.73	.10		16H-180F-

ODOR

RT	RT WEIGHT	CURE
A	B 00022.88	16H-180F-

TOXICITY

63009 POTTING COMPOUND PROSEAL 799 GID: BAXXXX

MANF: ESSEX CHEM CORP

SPEC: MIL-S-0024041

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.150	0.003	01.00	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006365 2

63009 POTTING COMPOUND PROSEAL 799 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.9E-6	9.90	6.30	.55	16H-180F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61759 POTTING COMPOUND REN RP6401A POLYURETHANE BLUE GID: BACQGS

MANF: CIBA-GEIGY SPEC: RP-6401-A

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	023.8	014.5	0.417	12.00	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-7	1.68	.04		6H-70F- 168H-46F- 16H-180F-

ODOR

RT	RT WEIGHT	CURE
A	B 00020.24	6H-70F- 16H-180F-

TOXICITY

61760 POTTING COMPOUND REN RP6402A POLYURETHANE RED GID: BACQGS

MANF: CIBA-GEIGY SPEC: RP-6402-A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	4	023.8	014.5	0.410			00.00	NONE
X	1	023.8	014.5	0.410		00.07	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	023.8	014.5	0.092	12.00	00.00

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.6E-7	2.35	.02		6H-70F- 16H-180F-

ODOR

RT	RT WEIGHT	CURE
A	V 00019.54	6H-70F- 16H-180F-

TOXICITY

06174 POTTING COMPOUND REZOLIN 185N POLYURETHANE GID: BACQXX

MANF: HEXCEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.050	0.003	00.00	00.00	NONE
B	1	020.9	014.7	0.050	0.003		07.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62427 POTTING COMPOUND RTV 11/C12 GID: BAXXXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.062		00.02	12.00	T MOD
X	1	025.9	014.3	0.062		00.50	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.3E-6	3.25	1.91	.03	72H-70F-

ODOR

RT	RT WEIGHT	CURE
A	B 00019.94	72H-70F-

TOXICITY

62426 POTTING COMPOUND RTV 11/C9811 GID: BAXXXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.062			02.90	NONE
C	1	025.9	014.3	0.062			12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.91	.55	.00	24H-302F-

ODOR

RT	RT WEIGHT	CURE
A	B 00019.92	72H-70F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006366 4

06441 POTTING COMPOUND SCOTCHCAST 10 EPOXY GID: BABGXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.054			02.20	MOD
X	1	025.9	014.3	0.054		00.30	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.78	1.17	3.15	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
B	00020.03	48H-70F-

80058 POTTING COMPOUND SCOTCHCAST 212 GID: 80058

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	024.5	014.5	0.005	0.003	0.2	08.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
B	21.758	24H-70F-

05229 POTTING COMPOUND SCOTCHCAST 221 GID: DACRXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.25	.02	.00	24H-122F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

61951 POTTING COMPOUND SCOTCHCAST 226 A/B GID: ABDWXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.011	0.003		02.00	NONE
C	1	025.9	014.3	0.011	0.003	00.33	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.80	.42		168H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00009.27	168H-70F- 24H-150F-

05654 POTTING COMPOUND SCOTCHCAST 235 EPOXY GID: BABGXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.20	.31	.00	6H-199F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

05464 POTTING COMPOUND SCOTCHCAST 247 GID: BABGXX

MANF: 3M CO SPEC: MIL-I-16923

PT A:1017&PT B:1025

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.018	0.003		04.70	NONE
X	1	030.0	010.0	0.067		00.30	12.00 T	MOD
I	2	030.0	010.0	0.073			00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.9E-6	1.10	.06		10H-203F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00032.25	10H-203F-

05533 POTTING COMPOUND SCOTCHCAST 250 EPOXY GID: BABGXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.111	0.003	00.05	11.70 T	MOD

FSC

RT	FLUID NAME
A	HYZE

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006367 6

05533 POTTING COMPOUND SCOTCHCAST 250 EPOXY (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.072			01.50	NONE
C	1	023.8	014.5	0.072		00.16	11.90	T NONE

FSC

RT	FLUID NAME
X	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.65	.01	.00	24H-167F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.01	3H-248F-

69799 POTTING COMPOUND SCOTCHCAST 251 GID: BABGXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010	0.005		04.90	NONE

FSC

No test data

OXYGEN COMP

No test data

THERMAL VACUUM STABILITY

No test data

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	28.04	

05405 POTTING COMPOUND SCOTCHCAST 281 EPOXY GID: BABGXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.120	0.003	00.00	00.00	NONE
C	1	023.8	014.5	0.120	0.003	00.10	11.80	T SMALL
C	2	030.0	010.0	0.080		00.01	10.00	NONE
C	1	030.0	010.0	0.080		00.30	12.00	T NONE

FSC

No test data

OXYGEN COMP

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.56	.08	.00	4H-266F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00022.08	3H-248F-

62381 POTTING COMPOUND SCOTCHCAST 5 EPOXY GID: BABGXX

MANF: 3M CO

THERMAL VACUUM STABILITY

No test data

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.86	24H-70F-

06091 POTTING COMPOUND SCOTCHCAST 8 GID: BABGXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.010		00.00	00.00	NONE
X	1	025.9	014.3	0.010		00.37	12.00	T MOD
X	2	100.0	020.2	0.010		00.30	12.00	T MOD

FSC

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	50	72	120	0.025	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.59	1.48	.00	48H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00016.24	48H-70F-

61002 POTTING COMPOUND SCOTCHCAST 8/DC3140 GID: BABGGK

MANF: 3M CO/SCOTCHCAST
DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.437			00.30	SMALL

FSC

No test data

OXYGEN COMP

No test data

05591 POTTING COMPOUND SCOTCHCAST 9 EPOXY GID: BAABXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.049	0.003	00.00	00.00	NONE

FSC

No test data

OXYGEN COMP

No test data

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006368 8 ■

05591 POTTING COMPOUND SCOTCHCAST 9 EPOXY (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	023.8	014.5	0.049	0.003	00.06	12.00	T SMALL
B	1	030.0	010.0	0.010	0.003		06.70	SMALL

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.1E-7	3.74	1.16		48H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00085.92	168H-70F- 24H-150F-

05583 POTTING COMPOUND SCOTCHCAST EC243EPX GID: BABGXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	009.0	0.202		00.04	12.00	T MOD

FSC

No test data

OXYGEN COMP

No test data

80985 POTTING COMPOUND SCOTCHCAST EC243EPX TOX RATE STUDY

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00024.85	168H-70F- 24H-150F-

06329 POTTING COMPOUND SCOTCHCAST XR5001 GID: AUBGXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		01.50	NONE
A	1	030.0	009.0	0.001	0.003		01.30	NONE

FSC

No test data

OXYGEN COMP

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.72	.00	.50	24H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00002.12	24H-70F-

05863 POTTING COMPOUND SCOTCHCAST XR5068 GID: BABGXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	009.0	0.155		00.11	12.00	T SMALL

FSC

No test data

OXYGEN COMP

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML	CURE
C	1.0E-6	.78	.38	. 0	20H-194F-

ODOR

RT

No test data

TOXICITY

RT	WEIGHT	CURE

06472 POTTING COMPOUND SIL PTK 16000-002 GID: AZXXXX

MANF: PTK CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.166			02.40	NONE
A	1	030.0	009.0	0.162			01.50	SMALL

FSC

No test data

OXYGEN COMP

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.33	

63301 POTTING COMPOUND STYCAST 1090 FR GID: BABGXX

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.24	.08		2H-212F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00022.50	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006369 T

00031 POTTING COMPOUND STYCAST 1090/C9 GID: BABGXX

MANF: EMERSON AND CUMING SPEC: MIL-I-1693

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.050		00.03	12.00	T NONE
X	1	030.0	010.0	0.050		00.60	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.97	.00	.43	72H-46F- 24H-248F- 2H-338F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00022.50	

05346 POTTING COMPOUND STYCAST 1095/17 EPOXY GID: BABGXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.011	0.003		06.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70		0	20
Z	MECH	15	72	-297	0.062	02	03
X	PNEU	1500		70		1	20
Z	MECH	1500	72	70	0.062	02	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	9.3E-6	9.29	5.32		3H-210F- 3H-325F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00024.50	3H-210F- 3H-325F-

02631 POTTING COMPOUND STYCAST 1266 GID: BAXXXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.004	0.003	00.50	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.2E-6	1.02	.06	.46	24H-70F- 24H-150F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

60319 POTTING COMPOUND STYCAST 1467 GID: BABGXX

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.14	.00	.00	16H-70F- 1H-171F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

05855 POTTING COMPOUND STYCAST 1970 GID: BABGXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.065	0.003		01.90	NONE
A	1	023.8	014.5	0.107	0.003		01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00166.36	4H-212F-

62076 POTTING COMPOUND STYCAST 2641-40/C9 GID: BABGXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006370 6

62076 POTTING COMPOUND STYCAST 2641-40/C9 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME
A	MMH
C	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

05271 POTTING COMPOUND STYCAST 2651/C11 GID: BABGXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.265	0.003		03.40	SMALL
A	1	030.0	009.0	0.260	0.003		05.60	SMALL
X	1	030.0	010.0	0.046		00.23	12.00	T MOD

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.1E-7	.34	.01		24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00019.76	SEE TVS CURE1

61467 POTTING COMPOUND STYCAST 2651/C9 GID: BABGXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.055		00.54	12.00	T MOD
X	1	030.0	010.0	0.133		00.10	12.00	T MOD

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.23	.01	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00022.54	24H-70F- 24H-150F-

80975 POTTING COMPOUND STYCAST 2651/C9 TOX RATE STUDY

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00020.34	2H-170F- 2H-220F-

05681 POTTING COMPOUND STYCAST 2651MM EPOXY GID: FCXXXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3				00.10	NONE

FSC: No test data

OXYGEN COMP: No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.69	.00	.31	48H-46F- 2.5H-212F-

ODOR

RT

No test data

TOXICITY

RT	WEIGHT	CURE

05635 POTTING COMPOUND STYCAST 2762/17 GID: BABGXX

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.27	.08	.00	2H-300F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00049.35	3H-200F- 3H-300F-

06451 POTTING COMPOUND STYCAST 2850FT/C11 GID: BAXXXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	0.120		00.10	12.00	T NONE

FSC: No test data

OXYGEN COMP: No test data

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006371 8

06451 POTTING COMPOUND STYCAST 2850FT/C11 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.125		00.00	00.00	NONE
X	1	025.9	014.3	0.125		00.10	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.1E-6	.23	.02	.08	16H-180F- 4H-300F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	129.32	

05257 POTTING COMPOUND STYCAST 2850FT/C9 GID: BABGXX

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.27	.00	.00	24H-70F- 4H-140F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00020.09	2H-150F-

62161 POTTING COMPOUND STYCAST 2850GT/24LV GID: BABHXX

MANF: EMERSON AND CUMING

....NO TEST DATA AVAILABLE....

80982 POTTING COMPOUND STYCAST 2850GT/24LV TOX RATE STUDY

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00019.79	

80257 POTTING COMPOUND STYCAST 2850GT/C11

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.85	.03	.00	40H-149F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

05248 POTTING COMPOUND STYCAST 2850GT/C9 GID: BABGXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.012	0.003		00.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.34	.00	.00	168H-77F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

63012 POTTING COMPOUND STYCAST 2850KT/24LV GID: BABMBG

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3			00.31	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.65	.09	.00	168H-70F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00033.92	

62319 POTTING COMPOUND STYCAST 2850KT/C11 GID: BABGXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.100		00.09	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.7E-6	00.51	00.05	00.08	16H-167F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00052.00	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006372 T

62319 POTTING COMPOUND STYCAST 2850KT/C11 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					4H-300F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE

63010 POTTING COMPOUND STYCAST 2850KT/C9 GID: BAXXX

MANF: EMERSON AND CUMING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.100		00.05	12.00	T SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.2E-6	.21	.02	.07	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	A	00037.00	

06418 POTTING COMPOUND STYCAST 3050/C9 GID: BAXXXX

MANF: EMERSON AND CUMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.75	.01	.00	72H-70F-
					1.5H-259F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

63779 POTTING COMPOUND SUMICERAM S10A GID: BAHKMA

MANF: SUMITOMO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	K	00043.40	

06401 POTTING COMPOUND SYLGARD 170 GID: BACKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.120			00.10	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.19	.27	.00	168H-70F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	V	00183.71	8H-70F-

20105 POTTING COMPOUND SYLGARD 182 GID: BACKXX

MANF: DOW CORNING

SPEC: MIL-I-81550

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.250		00.01	06.20	SMALL
C	1	023.8	014.5	0.250		00.02	12.00	T SMALL
X	1	030.0	009.0	0.071		00.17	12.00	T MOD

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.00	.59	.00	4H-150F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	X	00019.64	16H-150F-

05671 POTTING COMPOUND SYLGARD 183 GID: BAXXXX

MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.00	.61	.00	1H-212F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

05758 POTTING COMPOUND SYLGARD 184 GID: EXXXXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.165			05.00	SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006373 1

05758 POTTING COMPOUND SYLGARD 184 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002			02.80	NONE
A	1	025.9	014.3	0.040	0.003		01.20	SMALL
A	1	030.0	009.0	0.049	0.003		01.80	SMALL
A	1	033.0	014.3	0.040	0.003		06.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	1.55	4.65	.00	1H-212F- 47H-275F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
X	00021.32	

60191 POTTING COMPOUND SYLGARD 186 GID: BAXXXX

MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.19	.94	.00	24H-70F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

80022 POTTING COMPOUND TRIBO TDF5 GID: BAXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	14.7	72	-297	0.120	00	10

62033 POTTING COMPOUND TRIDOX F88 EPOXY GID: BABGXX

MANF: TRIDOX CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.70	.00		24H-70F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

64465 POTTING COMPOUND URETHANE GID: BACQXX

MANF: SPEC: MC7768-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.075		00.17	05.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20591 POWDER 8804 STAMPING BLUE GID: AWXXXX

MANF: CUTTERS EXCHANGE SPEC: ST80P764-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.010		01.10	NONE
A	1	033.0	014.3	0.001	0.010		01.10	NONE
A	1	100.0	020.2	0.001	0.010		00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00009.12	

63331 POWDER ALKALUME 1744 GID: DDXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	72	-220	0.020	0	20

20474 POWDER BIOSORB B210 GID: DDXXXX

MANF: ARBROOK INC SPEC: ST53P739

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006374 3

20474 POWDER BIOSORB B210 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	100.0	020.2	0.001	0.003		01.10	SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.10	

60288 POWDER CAB-O-SIL M5

MANF: CABOT CORP

....NO TEST DATA AVAILABLE....

63315 POWDER GRAPHITE P692 GID: DDGFXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	500	72	-297		04	20

60217 POWDER PROPELLANT GEN

....NO TEST DATA AVAILABLE....

20776 POWDER TALC

SPEC: MIL-T-50036

MANF:

....NO TEST DATA AVAILABLE....

61695 POWER SUPPLY UPM15/100 ASSEMBLY GID: EXGUXX

MANF: DATEL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00140.37	

61783 PRESSURE VESSEL COMPOSITE GID: BBCQMA

MANF: MARTIN MARIETTA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.312			02.50	MOD
X	1	023.8	014.5	0.312		00.04	05.00	T MOD
X	2	100.0	006.2	0.312		.	02.50	MOD
X	1	100.0	006.2	0.312		00.30	05.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	1.00	.04	.00	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

60051 PRIMER ZINC-SELE 9334 GREEN GID: AUXXXX

SPEC: 10A00528 P3.3

MANF: RUSTOLEUM

....NO TEST DATA AVAILABLE....

85396 PRINTED WIRING BOARD COPPER CLAD/POLYIMIDE GLASS/CAT-L-INK 50-100 MARKING 1 TO 3 MILS THICK/URALANE 5075 CONF

MANF: FURANE
HYSOL/DEXTER

SPEC: LAC37-4388-0202
MIL-9-55110

LAC40-4647
MIL-P-13949/13

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.103			02.87	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60212 PROPELLANT

SPEC: NAV ORD WS17360

MANF:

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006375 5

60133 PROPELLANT BSM U7P19048
MANF: AQM SPEC: SE0622
....NO TEST DATA AVAILABLE....

60132 PROPELLANT LINER BSM U7L004B
MANF: AQM SPEC: SE0729
....NO TEST DATA AVAILABLE....

60095 PROPELLANT LINER UF2137
MANF: THIOKOL SPEC: STW5-2676
....NO TEST DATA AVAILABLE....

60311 PROPELLANT PELLET
MANF: HI SHEER
....NO TEST DATA AVAILABLE....

60214 PROPELLANT SOLID
MANF: SPEC: K-SMK-01-2B TP-H-3282C

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	2.93	.14	.00		No test data		

60093 PROPELLANT TPH1148
MANF: THIOKOL SPEC: STW5-2683
....NO TEST DATA AVAILABLE....

60094 PROPELLANT TPH1154
MANF: THIOKOL SPEC: STW5-2673
....NO TEST DATA AVAILABLE....

61395 PUMP MICRO GID: FCXXXX

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data							K 00402.09	

05851 PURAFIL AL203/KMN04 INORGANIC
MANF: PURAFIL INC
....NO TEST DATA AVAILABLE....

60169 PUTTY ZINC CHROMATE 3992
MANF: SPEC: STW5-2847
....NO TEST DATA AVAILABLE....

60119 PUTTY ZINC CHROMATE GENERAL PURPOSE
MANF: SPEC: MIL-P-8116
....NO TEST DATA AVAILABLE....

85456 PWB COPPER CLAD GLASS FABRIC EPOXY RESIN FR4 COATED WITH HUMISEAL/INDICATOR MODEL 2495 ATTACHED TO BOARD GID: EXXXXX
MANF: WESTON INSTRUMENTS SPEC: P/N 2495-SW10082

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.375			04.00	T LARGE	No test data	No test data							

61116 RAZOR GILLETTE TRAC II GID: FCXXXX
MANF: GILLETTE

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data						A	K 00021.95	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006376 7

60746 RAZOR NORELCO ROTARY WITH CHARGER GID: FCXXXX
MANF: NORTH AMERICAN PHILIPS CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00529.70	

61310 RAZOR RECHARGEABLE XLR900 GID: FCXXXX
MANF: REMINGTON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00327.95	

20668 RAZOR SAFETY SUPER 84
MANF: GILLETTE
....NO TEST DATA AVAILABLE....

61311 RAZOR XLR500 GID: FCXXXX
MANF: REMINGTON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00132.73	

60236 RDX SPEC: MIL-R-398TACC
MANF:
....NO TEST DATA AVAILABLE....

61918 RECEPTACLE MS27503Y8E-35P GID: BCXXXX
MANF: BENDIX

SPEC: MIL-C-27599

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5			00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

MIL-C-3899

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.8E-7	1.22	.06		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

60701 RECORDER AUDIO 2625 GID: EZXXXX
MANF: CRAIG CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00475.16	

61285 RECORDER MARS 1400 GID: FBXXXX
MANF: BELL & HOWELL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	20200.80	

61059 RECORDER STRIP CHART GID: FCXXXX
MANF: WATANABE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	26254.00	

60925 RECORDER STRIP CHART/THERMAL/2 CHANNEL GID: FCXXXX
MANF: MFE CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	11284.00	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006377 9

69875 RED SHIELDING/SHEATH MATERIAL (PORTION FROM HYDROCARBON SAMPLE LINE)

MANF: NASA/KSC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	1.05	.38	.02	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

62001 REGULATOR OXYGEN GID: FEXXXX

MANF: VICTOR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	3000		70		0	40

61650 REGULATOR VICTOR SR250D

MANF: VICTOR

....NO TEST DATA AVAILABLE....

62247 RELEASE AGENT MS143 GID: BVXXXX

MANF: MILLER STEPHENSON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	14.20	9.96	.00	2H-46F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	X 00001.99	2H-70F-
		2H-70F-

62248 RELEASE AGENT MS143/DYEPEN GID: BVXXXX

MANF: SHANNON LUMINOUS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	X 00002.41	1H-70F-
		2H-70F-

60888 RELEASE AGENT X-AIR 4N002

MANF: ISOCHEM RESINS SPEC: ST80C78701

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
	X 00001.96	24H-70F-
		16H-150F-
		24H-150F-

80260 RESIN CALIBRE 700-4 POLYCARBONATE COLOR #030003 GID: ABXXXX

MANF: DOW CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.118			00.20	NONE
X	1	030.0	010.0	0.118		0.09	07.20	LARGE
X	2	033.0	010.0	0.118			00.40	NONE
X	1	033.0	010.0	0.118		0.02	10.40	LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.0E-6	.17	.02	.13	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
	K 21.401	

80208 RESIN CALIBRE 800-4 POLYCARBONATE .10 INCH SHEET STANDARD BLACK 770001 GID: ABXXXX

MANF: DOW CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	030.0	010.0	0.117			00.20	NONE
B	1	030.0	010.0	0.120		00.09	08.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.0E-6	.16	.01	.12	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
	K 22.103	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006378 0

62896 RESIN R2

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data	Z	MECH	400	72	-297	0.050	2	3

62140 RESIN RC2 IMPREGNATING GID: ABBGXX

MANF: IMPCO

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	020.9	014.7	0.180		00.05	11.80	T SMALL	No test data	No test data							

85461 RESIN SDP 1 SHEET DAMPING MATERIAL

MANF: NEC

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	024.5	014.5	0.100	0.032	00.03	12.0	T LARGE	No test data	No test data							
X	1	024.5	014.5	0.100	0.032	00.03	12.0	T LARGE									
X	1	025.9	014.3	0.100	0.032	00.04	12.0	T LARGE									

85460 RESIN SDP 1A POLYETHER EPOXY WITH PHTHALIC ACID ANHYDRIDE HARDENER

MANF: NEC

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	024.4	014.5	1.000		00.02	9.50	T LARGE	No test data	No test data							
X	1	24.5	014.5	1.000		00.02	9.50	T LARGE									

85462 RESIN SDP 2 BIS PHENOL A DAMPING MATERIAL

MANF: NEC

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	024.5	014.5	0.145	0.032	00.01	12.0	T LARGE	No test data	No test data							
X	1	024.5	014.5	0.145	0.032	00.01	12.0	T LARGE									
X	1	025.9	014.3	0.145	0.032	00.01	12.0	T LARGE									

85463 RESIN SDP 3 BROMINATED EPOXY WITH POLYAMIDEAMINE HARDENER

MANF: NEC

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	2	024.5	014.5	0.800		00.01	00.50	NONE	No test data	No test data							
A	1	024.5	014.5	0.800		00.05	02.00	NONE									

85464 RESIN SDP 3A BROMINATED EPOXY WITH POLYAMIDEAMINE HARDENER

MANF: NEC

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	2	024.5	014.5	1.000		00.01	0.125	NONE	No test data	No test data							
A	1	024.5	014.5	1.000		00.02	04.25	SMALL									

85465 RESIN SDP 4 BROMINATED EPOXY WITH POLYOXYARKYLENE POLYAMINE HARDENER

MANF: NEC

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	024.5	014.5	0.750		00.01	00.25	NONE	No test data	No test data							
C	1	024.5	014.5	0.750		00.01	12.0	T NONE									

85466 RESIN SDP 4A BROMINATED EPOXY WITH POLYOXYARKYLENE POLYAMINE HARDENER

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	2	024.5	014.5	1.000		00.01	00.13	NONE	No test data	No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006379 2

85466 RESIN SDP 4A BROMINATED EPOXY WITH POLYOXYAREKYLENE POLYAMINE HARDENER (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	1.000		00.03	1.125	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

69887 RETENTION OF HCI ON LAUNCH PLUME SAMPLER CHEMICAL FILTERS

MANF: NASA/KSC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
S	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61629 REVAC DD2010 GID: FCXXXX

MANF: ESA/ERNO SPEC: REVAC DG 2010

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.125			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63969 RING 60% BRONZE FILLED TFE

MANF: FLUOROCARBON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.060	0	20
B	MECH	14.7	72	297	0.060	0	20
B	PNEU	3500		72	0.060	0	20
X	PNEU	4000		72	0.060	1	02
B	MECH	4500	72	-297	0.060	00	20
X	PNEU	4500		72	0.060	1	05

63404 RING PLASTIC ON METAL DIODE

MANF: UNITRODE SPEC: ST318-15

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
S		024.5	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62854 ROD CHEMFLUOR TFE VIRGIN EXT GID: DMCNXX

MANF: CHEMPLAST

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	8800	58	-297	0.050	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.00	.00	.00	.08H-618F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20176 ROD CP2-4289 GID: DMBGXX

MANF: HYSOL/DEXTER SPEC: MIL-I-16923

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.319			02.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00020.05	

TOXICITY

62069 ROD REINFORCED GRAPHITE/PHENOLIC GID: DMGFBX

MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.32	.00		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006380 9

62150 ROD TEFLON/25% GLASS GID: DMCDIA
MANF: WHITFORD CORP

SPEC: L 0000R1153

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

L 0000R1161

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	-297	0.060	0	20
B	PNEU	1000		70	0.060	0	23
B	MECH	1500	72	-297	0.610	0	40
X	PNEU	1500		70	0.060	4	69
B	MECH	1500	72	70	0.610	0	80
X	PNEU	2000		70	0.060	1	44
B	PNEU	3000		70	0.060	0	40
X	PNEU	3500		70	0.060	3	34
X	PNEU	4000		70	0.060	2	18
X	PNEU	4500		70	0.060	1	03
X	PNEU	5000		70	0.060	1	01

06557 ROPE FIBERGLASS/TFE COATED SF200
MANF: SANTA FE TEXTILES
....NO TEST DATA AVAILABLE....

06112 ROPE SILICA SS1404 (INORGANIC)
MANF:
....NO TEST DATA AVAILABLE....

SPEC: MB0135-030

61667 RUBBER 10006149 GID: BHXXXX
MANF: SCOTT AVIATION

SPEC: NAS-9-15246

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.051			08.30	NONE
C	1	023.8	014.5	0.051		00.36	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT
A	A	00020.16

TOXICITY

CURE

84945 RUBBER 3-6550
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.52	.54	.00	168H-70F-

ODOR

RT	RT	WEIGHT
No test data		

TOXICITY

CURE

20586 RUBBER 4930-00-946-2916 GID: DOXXXX
MANF: GSA

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT
A	A	00006.61

TOXICITY

CURE

84680 RUBBER ABRASHUN 5015
MANF: DIKE-O-SEAL
....NO TEST DATA AVAILABLE....

84681 RUBBER ABRASHUN 5035
MANF: DIKE-O-SEAL
....NO TEST DATA AVAILABLE....

84683 RUBBER ABRASHUN 5040
MANF: DIKE-O-SEAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006381 0

84685 RUBBER ABRASHUN 5045
MANF: DIKE-O-SEAL
....NO TEST DATA AVAILABLE....

84687 RUBBER ABRASHUN 5055
MANF: DIKE-O-SEAL
....NO TEST DATA AVAILABLE....

84688 RUBBER ABRASHUN 5065
MANF: DIKE-O-SEAL
....NO TEST DATA AVAILABLE....

84689 RUBBER ABRASHUN 5075
MANF: DIKE-O-SEAL
....NO TEST DATA AVAILABLE....

84692 RUBBER ABRASHUN 5088
MANF: DIKE-O-SEAL
....NO TEST DATA AVAILABLE....

84694 RUBBER ABRASHUN 5095
MANF: DIKE-O-SEAL
....NO TEST DATA AVAILABLE....

84695 RUBBER ABRASHUN 5097
MANF: DIKE-O-SEAL
....NO TEST DATA AVAILABLE....

84698 RUBBER ABRASHUN 5098
MANF: DIKE-O-SEAL
....NO TEST DATA AVAILABLE....

05003 RUBBER AF-E332 EPR GID: DVDDXX
MANF: TRW

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.60	.09	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00010.05	

61186 RUBBER AGC 3-126 CLASS 5 GID: DOXXXX
MANF: AGC INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	PNEU	1000		70	.059	0	05
I	PNEU	1000		70	0.059	0	05
X	PNEU	10000		70	.070	1	01
X	PNEU	10000		70	0.070	1	01
B	PNEU	1500		70	.074	0	20
B	PNEU	1500		70	0.074	0	20
X	PNEU	2000		70	0.074	3	6
B	PNEU	4000		70	.073	0	20
B	PNEU	4000		70	0.073	0	20
X	PNEU	5000		70	.070	1	25
X	PNEU	5000		70	0.070	1	25
B	PNEU	6000		70	.070	0	25
B	PNEU	6000		70	0.070	0	25
B	PNEU	7000		70	.070	1	08
X	PNEU	7000		70	0.070	1	08

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006382 2

61186 RUBBER AGC 3-126 CLASS 5 (cont)

FLAMMABILITY							FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
									X	PNEU 8000		70	0.070	3	06

63746 RUBBER ALLOY L065-72A GID: DOXXXX
MANF: MCDONNELL DOUGLAS

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.4E-6	9.34	5.86	.22		No test data	

80193 RUBBER BAND NATURAL OR SYNTHETIC SIZE 64 GID: DOXXXX
MANF: GFE
SPEC: FSN 7510-00-2433435 SED33102094-301

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data						K	21.968	

84006 RUBBER BOYD NR35
MANF: BOYD INDUSTRY RUBBER
....NO TEST DATA AVAILABLE....

84007 RUBBER BOYD OR50
MANF: BOYD INDUSTRY RUBBER
....NO TEST DATA AVAILABLE....

84008 RUBBER BOYD OR60
MANF: BOYD INDUSTRY RUBBER
....NO TEST DATA AVAILABLE....

84009 RUBBER BOYD OR70
MANF: BOYD INDUSTRY RUBBER
....NO TEST DATA AVAILABLE....

63924 RUBBER BUMBER GID: DOXXXX
MANF: H H SMITH

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data						K	00003.16	

60130 RUBBER BUNA N GID: DPXXXX
MANF: 3M CO
QPL
SPEC: MIL-S-4383 SE0733

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	6.0E-6	11.31	1.45	.46		No test data	

20238 RUBBER BUNA N 5-565 GID: DOXXXX
MANF: PARKER SEAL
....NO TEST DATA AVAILABLE....

65499 RUBBER BUNA N FC776 GID: DOXXXX
MANF: 3M CO

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data						X	00001.87	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006383 4

84010 RUBBER BUNA N NBR50
MANF: BOYD INDUSTRY RUBBER
....NO TEST DATA AVAILABLE....

84011 RUBBER BUNA N NBR60
MANF: BOYD INDUSTRY RUBBER
....NO TEST DATA AVAILABLE....

84012 RUBBER BUNA N NBR70
MANF: BOYD INDUSTRY RUBBER
....NO TEST DATA AVAILABLE....

20437 RUBBER BUNA S GID: DOXXXX
MANF: BOYD INDUS RUBBER

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.125			01.10	NONE	No test data		No test data							
X	1	025.9	014.3	0.125		00.12	12.00	T MOD										

THERMAL VACUUM STABILITY					ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	6.0E-7	1.85	.79			A	A	00019.99	

84013 RUBBER BUNA S SBR75
MANF: BOYD INDUSTRY RUBBER
....NO TEST DATA AVAILABLE....

02966 RUBBER BUTYL GID: DVCZXX
MANF: STILLMAN RUBBER SPEC: MB0130-027T1

THERMAL VACUUM STABILITY					ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.0E-6	8.86	1.79	.00		A	V	00121.86	

03458 RUBBER BUTYL GID: DOCZXX
MANF: SPEC: MB0130-027

THERMAL VACUUM STABILITY					ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.0E-6	8.86	1.79	.00		No test data			

20165 RUBBER BUTYL GID: DOCZXX
MANF: SPEC: AMS 3239

THERMAL VACUUM STABILITY					ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.0E-6	8.86	1.79	8.83		No test data			

61539 RUBBER BUTYL GID: DOCZXX
MANF: ARROWHEAD PRODUCTS SPEC: AP2712

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	020.9	014.7	0.050			00.80	NONE	No test data		No test data							
X	1	020.9	014.7	0.050		00.20	12.20	T MOD										

62203 RUBBER BUTYL GID: CHCZXX
MANF: SPEC: AMS 3238

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									A	AMMONIA	No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006384 6

05810 RUBBER BUTYL 823-70 GID: DOCZXX

MANF: PLASTIC & RUBBER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.077			01.60	NONE
C	1	023.8	014.5	0.077		00.19	10.20	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05840 RUBBER BUTYL AP2712 CL RC615 GID: DOCZXX

....NO TEST DATA AVAILABLE....

05725 RUBBER BUTYL B318-70 GID: CHCZXX

MANF: SPEC: AMS 3238

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.16	.90	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06200 RUBBER BUTYL B59L-80 GID: CHCZXX

MANF: PARKER SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	6.0E-7	.51	.01		24H-125F-0psia1E-4

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05339 RUBBER BUTYL B612-70 GID: DOCZXX

MANF: PARKER SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.089		00.19	12.00	T MOD
X	2	030.0	010.0	0.080		00.05	02.50	NONE
X	1	030.0	010.0	0.080		00.10	11.80	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	10.31	1.05	.00	

ODOR

RT	RT WEIGHT	CURE
X	21.07	

TOXICITY

62402 RUBBER BUTYL B7764-11 GID: DOCZXX

MANF: AMERICAN SCIENTIFIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	K 00020.52	

TOXICITY

84014 RUBBER BUTYL IIR55

MANF: BOYD INDUSTRY RUBBER

....NO TEST DATA AVAILABLE....

06067 RUBBER BUTYL R/S 201-6 GID: DOCZXX

MANF: AQM
POWER SYSTEMS
ROYAL SEALS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	100	10	250	0.080	0	20
X	MECH	250	10	250	0.080	2	24
X	MECH	250	10	70	0.081	0	20
B	PNEU	500		250	0.080	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006385 8

06067 RUBBER BUTYL R/S 201-6 (cont)

FLAMMABILITY								FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
											B	PNEU	500		70	0.081	0	20
											Z	MECH	500	72	70	0.081	02	03
											B	PNEU	65		250	0.055	0	200
											X	MECH	65	10	250	0.066	0	20

84871 RUBBER CALTHANE 1400
MANF: CAL POLYMERS INC
....NO TEST DATA AVAILABLE....

84875 RUBBER CALTHANE 1700
MANF: CAL POLYMERS INC
....NO TEST DATA AVAILABLE....

84882 RUBBER CALTHANE 1900
MANF: CAL POLYMERS INC
....NO TEST DATA AVAILABLE....

84890 RUBBER CALTHANE ND1100
MANF: CAL POLYMERS INC
....NO TEST DATA AVAILABLE....

84892 RUBBER CALTHANE ND2300
MANF: CAL POLYMERS INC
....NO TEST DATA AVAILABLE....

84897 RUBBER CALTHANE ND3200
MANF: CAL POLYMERS INC
....NO TEST DATA AVAILABLE....

84901 RUBBER CALTHANE NF1200
MANF: CAL POLYMERS INC
....NO TEST DATA AVAILABLE....

34905 RUBBER CALTHANE NF1300
MANF: CAL POLYMERS INC
....NO TEST DATA AVAILABLE....

84909 RUBBER CALTHANE NF1300-60A
MANF: CAL POLYMERS INC
....NO TEST DATA AVAILABLE....

84912 RUBBER CALTHANE NF1500
MANF: CAL POLYMERS INC
....NO TEST DATA AVAILABLE....

84914 RUBBER CALTHANE NF2300
....NO TEST DATA AVAILABLE....

84917 RUBBER CALTHANE NF310W
MANF: CAL POLYMERS INC
....NO TEST DATA AVAILABLE....

06352 RUBBER CHLOROPRENE C873-70 GID: DQDBXX
MANF: PARKER SEAL

MSFC-HDBK-527 REV F ■ 9999942 0006386 T ■

Information Handling Services, 2000

06352 RUBBER CHLOROPRENE C873-70 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	1050	10	250	0.064	4	10
X	PNEU	1050		250	0.066	10	36
X	PNEU	1050		250	0.068	4	08
X	MECH	1050	10	250	0.072	0	20
X	MECH	1050	15	250	0.074	0	20
X	PNEU	1050		250	0.075	3	23
X	MECH	135	20	250	0.070	0	20
B	PNEU	250		250	0.065	0	20
X	PNEU	250		250	0.066	1	40
X	PNEU	500		250	0.064	2	23
X	PNEU	500		250	0.066	2	49
B	PNEU	500		250	0.075	0	40

20511 RUBBER CHLOROPRENE CPD 2408A GID: DODBXX

MANF: LATEX PRODUCTS

SPEC: ASTM D2000BC415

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.025			01.90	NONE
X	1	025.9	014.3	0.025		00.50	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-7	3.24	.93		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00019.52	

06409 RUBBER CHLOROPRENE NOC GID: DODBXX

MANF:

SPEC: SVHS 8509

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.026			00.60	NONE
C	1	025.9	014.3	0.026		00.50	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.38	.25	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.34	

62314 RUBBER CHLOROPRENE VONAR 3 GID: FJDBXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.300			03.10	NONE
I	1	025.9	014.3	0.300		00.13	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	1.35	.44		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.06	

84198 RUBBER CHOFOAM 1501

MANF: CHOMERICS

....NO TEST DATA AVAILABLE....

06042 RUBBER CHOSEAL 1214 WITH AG/SILICONE GID: DOCKXX

MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.26	.06	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006387 1

05558 RUBBER CHOSEAL 1217 FLUORO SILICONE/AG FILLED GID: CHDGXX

MANF: CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.030		00.22	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.6E-7	.25	.02		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00186.30	

05557 RUBBER CHOSEAL 1221 AG/FLUOROSILICONE GID: DOBPXX

MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.30	.01	.00	.25H-340F- 3H-351F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

05596 RUBBER CHOSEAL 1250REI/SIL/AG GID: CHCKMR

MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.71	.16	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00020.02	

05089 RUBBER CNR RESISTAZINE 88 GID: DOXXXX

MANF: COASTCRAFT RUBBER CO

....NO TEST DATA AVAILABLE....

05251 RUBBER COHRLASTIC 10480 SILICONE GID: CACKXX

MANF: CONN HARD RUBBER SPEC: AMS 3195

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.113	0.003		00.40	NONE
A	1	023.8	014.5	0.500			00.50	NONE
A	1	025.9	014.3	0.500			01.20	NONE
A	1	030.0	008.0	0.488			00.50	NONE
A	1	030.0	009.0	0.500		00.01	12.00	T SMALL
X	1	040.0	008.0	0.488			03.70	NONE
X	1	050.0	008.0	0.500		00.02	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		70	0.125	02	07
Z	MECH	1500	72	70	0.130	02	03

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.67	.26	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00209.03	

84163 RUBBER COHRLASTIC 300

MANF: CONN HARD RUBBER

....NO TEST DATA AVAILABLE....

85430 RUBBER COHRLASTIC 3111 GLASS REINFORCED SILICONE FILM GID: ABXXXX

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.011		00.07	02.00	NONE
A	1	030.0	010.2	0.011		00.14	03.75	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

84164 RUBBER COHRLASTIC 400

MANF: CONN HARD RUBBER

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006388 3

85417 RUBBER COHRLASTIC 4032 GLASS REINFORCED SILICONE SHEET GID: DOXXXX

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
I	1	024.5	014.5	0.035		0.021	12.0	T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65159 RUBBER COHRLASTIC 4050 SILICONE GLASS GID: DOCKFV

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	024.5	014.5	0.052			05.75		NONE
A	1	024.5	014.5	0.020		00.03	5.50		NONE
I	1	025.9	014.3	0.052		00.01	12.00	T	NONE
B	2	025.9	014.3	0.020		00.01	5.50		NONE
B	1	025.9	014.3	0.020		00.03	7.25		NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	.63	.19	.05	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00021.20	

85483 RUBBER COHRLASTIC 4150 SILICONE/GLASS

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.071			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

84165 RUBBER COHRLASTIC 500

MANF: CONN HARD RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.90	.59	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

84166 RUBBER COHRLASTIC 600

MANF: CONN HARD RUBBER

....NO TEST DATA AVAILABLE....

61969 RUBBER COHRLASTIC 700 SILICONE GID: DOCRXX

MANF: CONN HARD RUBBER SPEC: AMS 3304

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	030.0	008.0	0.130			02.00		NONE
I	1	040.0	008.0	0.130		00.02	12.00	T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-7	.97	.40		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00053.20	

84167 RUBBER COHRLASTIC 9030

MANF: CONN HARD RUBBER

....NO TEST DATA AVAILABLE....

84168 RUBBER COHRLASTIC 9040

MANF: CONN HARD RUBBER

....NO TEST DATA AVAILABLE....

84169 RUBBER COHRLASTIC 9050

MANF: CONN HARD RUBBER

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006389 5

84170 RUBBER COHRLASTIC 9070
MANF: CONN HARD RUBBER
....NO TEST DATA AVAILABLE....

62133 RUBBER COHRLASTIC 9235 GID: DVOPXX
MANF: CONN HARD RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.4E-7	.81	.24		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

80822 RUBBER COHRLASTIC 9255
MANF: CONN HARD RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.77	.29	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

80823 RUBBER COHRLASTIC 9275
MANF: CONN HARD RUBBER
....NO TEST DATA AVAILABLE....

80824 RUBBER COHRLASTIC 9750
MANF: CONN HARD RUBBER
....NO TEST DATA AVAILABLE....

80825 RUBBER COHRLASTIC 9770
MANF: CONN HARD RUBBER
....NO TEST DATA AVAILABLE....

80826 RUBBER COHRLASTIC 9855
MANF: CONN HARD RUBBER
....NO TEST DATA AVAILABLE....

80827 RUBBER COHRLASTIC R10450
MANF: CONN HARD RUBBER
....NO TEST DATA AVAILABLE....

05702 RUBBER COHRLASTIC R10460 SILICONE GID: DOCKXX
MANF: BOYD INDUS RUBBER
CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.162		00.00	00.00	NONE
A	1	023.8	014.5	0.245			02.50	NONE
X	2	023.8	014.5	0.070			02.40	MOD
X	1	023.8	014.5	0.070		00.80	12.00	T MOD
C	2	023.8	014.5	0.125			00.30	NONE
C	1	023.8	014.5	0.125			12.00	T NONE
A	1	030.0	009.0	0.500			00.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.6E-7	.05	.02		16H-480F-

ODOR

RT	RT WEIGHT	CURE
X	00020.06	

TOXICITY

05340 RUBBER COHRLASTIC R10470 SILICONE GID: DOCKXX
MANF: CONN HARD RUBBER
KIRKHILL RUBBER

SPEC: AMS 3195 AMS 3196

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.515			00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006390 1

05340 RUBBER COHRLASTIC R10470 SILICONE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.500			00.70	NONE
I	1	025.9	014.3	0.132		00.10	12.00 T	SMALL
B	2	025.9	014.3	0.217			00.10	NONE
B	1	025.9	014.3	0.217		00.03	06.40	NONE
C	1	025.9	014.3	0.250		00.03	10.30 T	NONE
B	2	025.9	014.3	0.130		00.04	01.30	NONE
B	1	025.9	014.3	0.130		00.065	09.03	NONE
A	1	030.0	009.0	0.500			01.20	NONE
C	2	030.0	010.0	0.125		00.01	08.00	NONE
C	1	030.0	010.0	0.125		00.10	12.00 T	NONE
B	2	030.0	010.0	0.197			00.10	NONE
B	1	030.0	010.0	0.197		00.03	07.00	SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.12	.05	.00	24H-360F-

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.94	

85418 RUBBER COHRLASTIC X4052 GLASS REINFORCED SILICONE SHEET GID: DOXXXX

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.045		00.02	01.50	NONE

THERMAL VACUUM STABILITY

No test data

FSC

No test data

OXYGEN COMP

No test data

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	18.7	

05980 RUBBER CONSIL 2 SILICONE/AG FILLED GID: CHCKMR

MANF: TECKNIT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.206			00.10	NONE
X	1	023.8	014.5	0.206		00.02	12.00 T	MOD

THERMAL VACUUM STABILITY

No test data

FSC

No test data

OXYGEN COMP

No test data

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00018.12	

05467 RUBBER CONSIL 861 SILICONE/CARBON FILLED GID: CHCKFO

MANF: TECHNICAL WIRE PROD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.034			00.40	SMALL
C	1	023.8	014.5	0.034		00.13	12.00 T	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.5E-6	.44	.13		

FSC

No test data

OXYGEN COMP

No test data

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00062.35	

83154 RUBBER CONSIL C875 CONDUCTIVE FLUOROSILICONE

MANF: TECKNIT

....NO TEST DATA AVAILABLE....

83156 RUBBER CONSIL R HT

MANF: TECKNIT

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006391 3

83155 RUBBER CONSIL R854 CONDUCTIVE FLUOROSILICONE
MANF: TECKNIT
....NO TEST DATA AVAILABLE....

61240 RUBBER DIATHON WATERPROOFING GID: DOAKXX
MANF: UNITED PAINT MFG

FLAMMABILITY								FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
		020.9	012.3		0.003			NONE	No test data		No test data							

83117 RUBBER DUOTHANE M1545A
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83118 RUBBER DUOTHANE M1545B
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83119 RUBBER DUOTHANE M1545C
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83120 RUBBER DUOTHANE M1545D
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83121 RUBBER DUOTHANE M4209
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83122 RUBBER DUOTHANE M6766
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83123 RUBBER DUOTHANE S300
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83124 RUBBER DUOTHANE S401
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83125 RUBBER DUOTHANE S502
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83126 RUBBER DUOTHANE S504
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83127 RUBBER DUOTHANE S600
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83128 RUBBER DUOTHANE S601
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006392 5

83129 RUBBER DUOTHANE S602
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83130 RUBBER DUOTHANE S603 (REDCOTE)
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83131 RUBBER DUOTHANE S700
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83132 RUBBER DUOTHANE S701
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83133 RUBBER DUOTHANE S702
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83134 RUBBER DUOTHANE S800
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83135 RUBBER DUOTHANE S802
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83136 RUBBER DUOTHANE S803
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83137 RUBBER DUOTHANE S900
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83138 RUBBER DUOTHANE S901
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

64005 RUBBER DYAD 606 GID: DOXXXX
MANF: SOUNDCRAFT INC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.4E-6	1.01	.01	.77		No test data		

84456 RUBBER ECCOTHANE 7510
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84457 RUBBER ECCOTHANE CPC18
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84458 RUBBER ECCOTHANE CPC19
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006393 7

84459 RUBBER ECCOTHANE CPC39
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

84460 RUBBER ECCOTHANE CPC41
MANF: EMERSON AND CUMING
....NO TEST DATA AVAILABLE....

82503 RUBBER EP6923
MANF: RM INDUSTRIAL PRODUCTS
....NO TEST DATA AVAILABLE....

62479 RUBBER EPDM 12045-01 GID: HDDDXX
MANF: SCOTT AVIATION

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	70	72	250	0.070	2	2

63500 RUBBER EPDM MOC GID: DOXXXX
MANF: FRANK MURKEN INC
KIRKHILL RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00016.90	

64869 RUBBER EPMD264
MANF: LIFE LIMITED
....NO TEST DATA AVAILABLE....

83834 RUBBER EPOXICAL 840A
MANF: USG INDUSTRIES
....NO TEST DATA AVAILABLE....

83835 RUBBER EPOXICAL 885A
MANF: USG INDUSTRIES
....NO TEST DATA AVAILABLE....

05814 RUBBER EPR 3177 GID: DODDXX
MANF: PRECISION RUBBER

SPEC: ASTM D2000BA715 B13C12F19 B-13,C12,F19

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.090			12.00	T MOD
X	1	023.8	014.5	0.090		00.12	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00019.98	

65314 RUBBER EPR 5708 GID: DODDXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.8E-6	1.10	.22	.14	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05395 RUBBER EPR AF-E411 GID: DODDXX
MANF: TRW
....NO TEST DATA AVAILABLE....

SPEC: MB0130-132

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006394 9

61838 RUBBER EPR AP3013 GID: CHDDXX

MANF: ARROWHEAD PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.156		00.06	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.3E-6	4.64	1.62		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61811 RUBBER EPR AS014 GID: DODDXX

MANF: FEDERAL-MOGUL SPEC: NAT 666014

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

01455 RUBBER EPR E515-80 GID: CHDDXX

MANF: PARKER SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.072		00.05	02.00	NONE
X	1	030.0	010.0	0.072		00.15	11.90	T MOD

FSC

RT	FLUID NAME
S	
A	AMMONIA

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.071	02	19
X	PNEU	1000		70	0.071	2	19
X	PNEU	2500		70	0.071	02	02
X	PNEU	2500		70	0.071	2	02
X	PNEU	3000		70	0.071	02	03
X	PNEU	3000		70	0.071	2	03
B	PNEU	500			0.071	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.95	.69	.00	

ODOR

RT	RT WEIGHT	CURE
A	A 00135.79	

TOXICITY

20093 RUBBER EPR E529-6 GID: DQDDXX

MANF: PARKER SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	100	72	250	0.058	2	3
B	PNEU	250		250	0.057	0	20
Z	MECH	250	72	70	0.058	04	05
X	MECH	500	10	70	0.058	0	20

61126 RUBBER EPR E617-9 ELASTOMER GID: DODDXX

MANF: PARKER SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.050	4	08
X	PNEU	1500		70	0.050	1	02
B	PNEU	500		70	0.050	0	20

05145 RUBBER EPR E688-70 GID: DODDXX

MANF: PARKER SEAL SPEC: MIL-G-22050

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.045		00.16	05.80	T MOD
C	2	030.0	010.0	0.070		00.06	02.30	NONE
C	1	030.0	010.0	0.070		00.10	01.60	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.045	2	08
Z	MECH	1000	72	70	0.045	01	01
X	MECH	14.7	72	-297	0.045	02	06
X	MECH	147	72	-297	0.045	02	06
X	PNEU	1500		70	0.045	2	02
Z	MECH	250	72	70	0.045	01	01

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006395 0

05145 RUBBER EPR E688-70 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	500		70	0.045	0	20
Z	MECH	500	72	70	0.045	01	01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.6E-6	2.91	.68		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00140.98	

05333 RUBBER EPR E692-75 GID: DODDXX
MANF: PARKER SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.086			12.00	T SMALL
X	1	030.0	010.0	0.070		00.14	11.70	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	14.7	72	-297	0.087	1	20
X	PNEU	1500		70	0.087	2	04
X	MECH	1500	25	70	0.087	00	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-7	2.18	1.03		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00164.11	

20237 RUBBER EPR E740-75 GID: DODDXX
MANF: PARKER SEAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE
X	00020.11	

20234 RUBBER EPR E798-70 GID: DOBOXX
MANF: PARKER SEAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.7E-6	1.92	.43	.24	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00020.67	

61468 RUBBER EPR E810-80 GID: CHDDXX
MANF: PARKER SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.087		00.11	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	1500	35	70	0.087	00	20
X	PNEU	1500		70	0.087	2	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.4E-7	1.21	.37		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00078.22	

06485 RUBBER EPR ER-WR-EPDM GID: AZDDXX
MANF: SCOTT AVIATION

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	65	60	220	0.029	0	20

62454 RUBBER EPR MARVEL SEAL 1312 GID: CHDDXX
MANF: LUDLOW CORP

SPEC: MIL-B-131FC2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE
	N2O4
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006396 2

05278 RUBBER EPR NOC GID: DODDXX
MANF: AQM
....NO TEST DATA AVAILABLE....

06291 RUBBER EPR NCLS1 GID: DODDXX
MANF: SCOTT AVIATION
....NO TEST DATA AVAILABLE....

61814 RUBBER EPR ORINGS NS014 E59 GID: DODDXX
MANF: FEDERAL-MOGUL

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									A	HYZE	No test data							
									C	HYZE								

84015 RUBBER EPT60
MANF: BOYD INDUSTRY RUBBER
....NO TEST DATA AVAILABLE....

80997 RUBBER ESTANE 58013
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81866 RUBBER ESTANE 58092
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

80998 RUBBER ESTANE 58110
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81867 RUBBER ESTANE 58122
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81868 RUBBER ESTANE 58130
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81869 RUBBER ESTANE 58133
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81870 RUBBER ESTANE 58134
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81871 RUBBER ESTANE 58137
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81872 RUBBER ESTANE 58206
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81873 RUBBER ESTANE 58271
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006397 4

81874 RUBBER ESTANE 58277
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81875 RUBBER ESTANE 58309
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81876 RUBBER ESTANE 58311
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81877 RUBBER ESTANE 58360
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81878 RUBBER ESTANE 58370
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

80999 RUBBER ESTANE 58600
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81000 RUBBER ESTANE 58610
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81879 RUBBER ESTANE 58630
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81880 RUBBER ESTANE 58810
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81881 RUBBER ESTANE 58863
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81882 RUBBER ESTANE 58881
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81883 RUBBER ESTANE 58887
MANF: B F GOODRICH
....NO TEST DATA AVAILABLE....

81481 RUBBER EYPEL F4001
MANF: ETHYL CORP
....NO TEST DATA AVAILABLE....

81482 RUBBER EYPEL F6504
MANF: ETHYL CORP
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F
9999942 0006398 6
Information Handling Services, 2000

81483 RUBBER EYPEL F7001
MANF: ETHYL CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.47	.46	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

81484 RUBBER EYPEL F7003
MANF: ETHYL CORP
....NO TEST DATA AVAILABLE....

81485 RUBBER EYPEL F7005
MANF: ETHYL CORP
....NO TEST DATA AVAILABLE....

81486 RUBBER EYPEL F7509
MANF: ETHYL CORP
....NO TEST DATA AVAILABLE....

81487 RUBBER EYPEL F8003
MANF: ETHYL CORP
....NO TEST DATA AVAILABLE....

81488 RUBBER EYPEL F9003
MANF: ETHYL CORP
....NO TEST DATA AVAILABLE....

05802 RUBBER FAIRPRENE 5159 GID: DOXXXX
MANF: DUPONT

SPEC: ST37V597-01

VZ-5151-420

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		00.80	NONE
A	1	025.9	014.3	0.005	0.003		02.30	SMALL
A	1	030.0	010.0	0.004			01.30	SMALL
A	1	033.0	014.3	0.005	0.003		04.80	SMALL
X	2	100.0	020.2	0.005	0.003	00.28	12.00	T NONE
X	1	100.0	020.2	0.005	0.003	01.27	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.9E-7	4.39	2.12	.00	16H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
A	B 00017.80	APPLY 4 SUCCESSIVE BRUSH COATS/CURE 30 MINUTES @ 70F BETWEEN EACH COATS. 16H-70F-AFTER FINAL COAT. RAISE TEMP. TO 220F/@ 50F PER HOUR. 8H-220F-

TOXICITY

61346 RUBBER FAIRPRENE DS0001 GID: DOHDXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.062		00.44	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	A 00021.01	

TOXICITY

62226 RUBBER FAIRPRENE SR554D GID: DOCKXX
MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	K 00001.32	

TOXICITY

02887 RUBBER FLUOREL 1062 GID: DODEXX
MANF: MOSITES RUBBER SPEC: MB0130-084T2

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.38	.03	.00	

ODOR TOXICITY

RT	RT WEIGHT	CURE
No test data		

03462 RUBBER FLUOREL 1066 GID: ABDEXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

03473 RUBBER FLUOREL 1079K GID: DODEXX
MANF: 3M CO
MOSITES RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.235			00.70	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	14.7	72	-297	0.229	2	9
X	PNEU	1500		70	0.236	1	06
X	PNEU	1500		70	0.236	1	6

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.38	.12	.00	

ODOR TOXICITY

RT	RT WEIGHT	CURE
No test data		

03046 RUBBER FLUOREL 2231 GID: DVDEXX
MANF: 3M CO
RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.090			00.10	SMALL
A	1	030.0	010.0	0.090			00.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	.07	.03		

ODOR TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.04	

05798 RUBBER FLUOREL 3217 GID: DVDEXX
MANF: 3M CO
RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.8	014.3	0.070			00.30	NONE
A	1	030.0	014.3	0.070			01.20	NONE
A	1	033.2	015.5	0.070			00.20	NONE
X	1	035.0	014.3	0.072			01.70	MOD
I	1	040.0	014.3	0.070		00.08	12.00	T NONE
X	1	050.0	014.3	0.070		00.07	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	500		250	0.068	0	20
X	MECH	500	10	250	0.068	0	20
B	PNEU	500		70	0.071	0	20
X	MECH	500	10	70	0.071	0	20

05428 RUBBER FLUOREL 4500 GID: BBDEXX
MANF: 3M CO
COX & CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.038			00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.4E-6	.42	.01		

ODOR TOXICITY

RT	RT WEIGHT	CURE
	A 00020.38	

61099 RUBBER FLUOREL 5033 GID: DVDEXX
MANF: 3M CO SPEC: STM0564-020302

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006400 0

61099 RUBBER FLUOREL 5033 (cont)

MANF: RAYBESTOS-MANHATTAN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.18	.05	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

61875 RUBBER FLUOREL 5767-1 GID: DVDEXX

MANF: 3M CO
RAYBESTOS-MANHATTAN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.67	.09	.50	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00010.07	

61876 RUBBER FLUOREL 5823 GID: DVDEXX

MANF: 3M CO
RAYBESTOS-MANHATTAN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.8E-6	.08	.00		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00010.09	

05230 RUBBER FLUOREL FC2170 GID: DVDEXX

MANF: 3M CO

SPEC: HK-CWB-1-1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.200			00.10	NONE
I	1	033.0	014.3	0.200		00.03	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1000	72	70	0.081	1	01
B	PNEU	2500		70	0.081	0	20
X	PNEU	3000		70	0.081	1	20
Z	MECH	3000	72	70	0.081	1	04
Z	MECH	4000	72	70	0.081	1	03
B	MECH	500	72	70	0.081	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.67	.23	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.02	

60423 RUBBER FLUOREL FC2174 GID: DVDEXX

MANF: 3M CO
PIERCE-ROBERTS

SPEC: AMS 7276
MIL-R-83248C1

AMS 7280

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	5500	72	70	0.060	00	120

62167 RUBBER FLUOREL V23 GID: DVDEXX

MANF: 3M CO
NATIONAL SEAL

SPEC: MIL-R-83248

MIL-R-83248T1C2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	PNEU	3000		70	0.074	0	03
B	PNEU	4000		70	0.074	0	20
X	PNEU	4500		70	0.074	0	01
X	PNEU	4500		70	0.074	1	01
X	PNEU	5000		70	0.074	1	05

61626 RUBBER FLUOROCARBON GID: DOEFXX

MANF: PARKER SEAL

SPEC: MIL-R-83248
MS83248/2-904

MS83248/1-916
STW3-3353A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1000	72	-297	0.111	2	21

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006401 2

61626 RUBBER FLUOROCARBON (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1000	72	70	0.111	2	12
Z	MECH	1000	70	72	0.500	2	6
Z	MECH	14.7	72	-297	0.111	11	13
B	MECH	14.7	72	-297	0.112	0	20
Z	MECH	14.7	72	-297	0.500	5	8
C	MECH	1500	50	-297	0.111	0	20
Z	MECH	1500	72	70	0.111	1	5
Z	MECH	2000	72	70	0.111	1	1
Z	MECH	2000	72	70	0.500	1	9
Z	MECH	2500	72	70	0.500	1	5
Z	MECH	3500	72	70	0.500	1	1
B	MECH	500	72	-297	0.111	0	20
B	MECH	500	72	70	0.111	0	20
B	MECH	500	72	70	0.500	0	20
X	MECH	6000	15	70	0.111	0	20
Z	MECH	6000	50	70	0.500	02	18

05797 RUBBER FLUOROCARBON 102-7 GID: CHEFHD

MANF: ROYAL SEALS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	500	10	250	0.063	00	20
B	PNEU	500		250	0.064	0	20
B	PNEU	500		70	0.059	0	20
X	MECH	500	10	70	0.059	00	20

61708 RUBBER FLUOROELASTOMER 2401B GID: DVDEXX

MANF: MOSITES RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	031.0	010.0	0.025			00.40	NONE
A	1	043.2	008.0	0.025			00.30	NONE

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT	RT	WEIGHT	CURE
A	X	00037.03	

TOXICITY

62066 RUBBER FLUOROELASTOMER O-RING GID: DODEXX

MANF: PRECISION RUBBER

SPEC: MIL-R-83248C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	100	72	-297	0.102	0	0
B	MECH	100	72	-297	0.102	0	20

05233 RUBBER FLUOROSILICONE GID: DODGXX

MANF: AQM
PRECISION RUBBER

SPEC: AMS 7273

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.050		00.40	07.00	T MOD
I	1	025.9	014.3	0.056		00.11	05.80	T SMALL

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT	RT	WEIGHT	CURE
A	V	00020.16	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006402 4

05728 RUBBER FLUOROSILICONE GID: DODPXX

MANF: SPEC: MIL-R-25988T2C1

....NO TEST DATA AVAILABLE....

61469 RUBBER FLUOROSILICONE GID: CHDPXX

MANF: LORD CORP SPEC: MIL-R-25988
LORD KINEMATICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.077			00.30	NONE
C	1	025.9	014.3	0.077		00.07	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.33	.02		

ODOR

RT	RT WEIGHT	CURE
A	K 00020.35	

TOXICITY

06484 RUBBER FLUOROSILICONE 16438-1 GID: DODGXX

....NO TEST DATA AVAILABLE....

06276 RUBBER FLUOROSILICONE 67XX GID: EGBPCK

MANF: KIRKHILL RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	020.9	014.7	0.180		00.12	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.2E-6	.57	.07		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06303 RUBBER FLUOROSILICONE 9-5400 GID: DOCKXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.10	.04	.00	16H-450F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06283 RUBBER FLUOROSILICONE 9-6500 GID: DOCKXX

MANF: BENDIX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.072			01.80	NONE
X	1	025.9	014.3	0.072		00.10	11.60	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.10	.03	00	

ODOR

RT	RT WEIGHT	CURE
A	A 00020.15	

TOXICITY

05095 RUBBER FLUOROSILICONE L449-65 GID: CHDGXX

MANF: PARKER SEAL SPEC: AMS 3326 MIL-R-25988/1
MIL-R-25988C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.093		00.08	12.00	T SMALL
C	2	030.0	010.0	0.070			02.70	NONE
C	1	030.0	010.0	0.070		00.10	11.70	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1000	72	70	0.084	2	02
X	PNEU	1000		70	0.088	2	33
Z	MECH	1500	72	70	0.101	2	02
X	PNEU	1500		70	0.107	2	10
Z	MECH	500	72	70	0.084	2	02
B	PNEU	500		70	0.088	0	20
B	PNEU	500		70	0.100	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.53	.07	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006403 6

05094 RUBBER FLUOROSILICONE L677-70 GID: CHDGXX

MANF: PARKER SEAL

SPEC: MIL-R-25988 MIL-R-25988C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.050		00.12	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.066	0	22
X	PNEU	1500		70	0.058	2	02
C	MECH	1500	30	70	0.066	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.5E-5	.31	.12		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20564 RUBBER FLUOROSILICONE L737-65 GID: CHEGHD

MANF: PARKER SEAL

SPEC: MIL-R-25988T1C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025:9	014.3	0.095		00.10	11.50	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.2E-6	.47	.04		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.42	

TOXICITY

05536 RUBBER FLUOROSILICONE L806-80 GID: CHDGXX

MANF:

SPEC: MIL-R-25988C1

....NO TEST DATA AVAILABLE....

61328 RUBBER FLUOROSILICONE LS2323 GID: DOXXXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1000	72			01	01
B	PNEU	1000		70		0	20
X	PNEU	1500		70		5	20
X	PNEU	2000		70		1	12
X	PNEU	3000		70		1	01
X	MECH	500	10			01	05

05276 RUBBER FLUOROSILICONE LS53 GID: DODGXX

MANF: DOW CORNING

SPEC: MIL-R-25988

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.092		00.07	12.00	T NONE
X	2	023.8	014.5	0.090			01.20	MOD
X	1	023.8	014.5	0.090		00.06	05.80	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	45	72	70	0.130	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.6E-7	.38	.04	.00	

ODOR

RT	RT WEIGHT	CURE
A	A 00020.11	

TOXICITY

05277 RUBBER FLUOROSILICONE LS63 GID: DOEGXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.078		00.08	05.80	T SMALL
I	1	025.9	014.3	0.075		00.07	05.80	T SMALL
I	1	030.0	014.3	0.070		00.10	05.70	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70	0.070	0	20
C	MECH	1500	35	70	0.070	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-7	.43	.00		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.07	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006404 8 ■

06490 RUBBER FLUOROSILICONE MS55 GID: DODGXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.37	.07	.35	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20395 RUBBER FLUOROSILICONE NE4240 GID: CHHDXX

MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.123			00.10	NONE
C	1	025.9	014.3	0.123		00.02	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.96	.38	.00	

ODOR

RT	RT WEIGHT	CURE
A	V 00019.96	

TOXICITY

20393 RUBBER FLUOROSILICONE NE6060 GID: CHHDXX

MANF: NICHOLS ENGINEERING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.120			01.20	MOD
X	1	025.9	014.3	0.120		00.08	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-7	.39	.02		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.01	

TOXICITY

20619 RUBBER FLUOROSILICONE NE6072 GID: CHDGHD

MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.160			00.20	NONE
X	1	025.9	014.3	0.160		00.05	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.4E-6	.74	.07		

ODOR

RT	RT WEIGHT	CURE
A	A 00083.56	

TOXICITY

20392 RUBBER FLUOROSILICONE NE7070G GID: CHHDXX

MANF: NICHOLS ENGINEERING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.138		00.01	12.00	T MOD
X	1	025.9	014.3	0.138		00.09	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	9.0E-7	4.85	.32		

ODOR

RT	RT WEIGHT	CURE
A	V 00019.87	

TOXICITY

20494 RUBBER FLUOROSILICONE NE7075 GID: CHHDXX

MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.143			01.20	NONE
C	1	025.9	014.3	0.143		00.11	11.90	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.55	1.18		

ODOR

RT	RT WEIGHT	CURE
A	V 00020.21	

TOXICITY

05200 RUBBER FLUOROSILICONE RTV 733 GID: DPEGXX

MANF: DOW CORNING

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006405 T

05200 RUBBER FLUOROSILICONE RTV 733 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.101			00.10	NONE
C	1	023.8	014.5	0.101			01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00016.93	24H-70F- 24H-150F-

81843 RUBBER GC202 CLASS B

MANF: GOAL CHEMICAL SEALANTS CORP

....NO TEST DATA AVAILABLE....

64238 RUBBER HOSE LOW PRESSURE

MANF: IMPERIAL CLEVITE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K		

81491 RUBBER JAMAK 7176

MANF: EUTSLER TECHNICAL PROD

....NO TEST DATA AVAILABLE....

62879 RUBBER KALREZ 1004 GID: DODEXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	10000	72	-220	0.070	3	3
X	MECH	10000	25	68	0.025	03	03
B	MECH	2000	72	-220	0.087	02	02

80301 RUBBER KALREZ 1018

MANF: DUPONT

....NO TEST DATA AVAILABLE....

05997 RUBBER KALREZ 1045 GID: DODEXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE
A	MMH
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	10000	72	-220	0.025	0	20
X	MECH	10000	72	-220	0.070	02	02
C	MECH	10000	51	77	0.070	0	20
B	MECH	2000	72	-220	0.025	0	20
B	MECH	3000	72	-220	0.025	0	20
X	MECH	3000	72	-220	0.070	02	02
X	MECH	4000	72	-220	0.070	02	02
B	MECH	500	72	-220	0.070	0	20
B	MECH	5000	72	-220	0.025	0	20
X	MECH	5000	72	-220	0.070	01	03

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.26	.02	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

63325 RUBBER KALREZ 1045R GID: DODEXX

MANF: DUPONT

SPEC: E 14653-8C1 E 14653-8C2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	5000	72	-220	0.085	02	07

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006406 1

63325 RUBBER KALREZ 1045R (cont)

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
										Z	MECH	5000	72	-220	0.087	02	02

63326 RUBBER KALREZ 1046R GID: DODEXX
MANF: DUPONT

SPEC: E 14653-8A1 — E 14653-8A2

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data	Z	MECH	5000	72	-220	0.087	02	02

62908 RUBBER KALREZ 1046R2 GID: DODEXX
MANF: DUPONT

SPEC: E 14653-8D1 — E 14653-8D2

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data	Z	MECH	5000	72	-220	0.075	04	06

62909 RUBBER KALREZ 1046R2M GID: DODEXX
MANF: DUPONT

SPEC: E 14653-8E1 — E 14653-8E2

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data	Z	MECH	5000	72	-220	0.093	04	04

63327 RUBBER KALREZ 1046RM GID: DODEXX
MANF: DUPONT

SPEC: E 14653-8B1 — E 14653-B2

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data	Z	MECH	5000	72	-220	0.075	2	2

05913 RUBBER KALREZ 1050 GID: DODEXX
MANF: DUPONT

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	023.8	014.5	0.056			00.20	MOD	A HYZE	B	MECH	414.7	72	-290	0.187	0	20

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	7.0E-7	.11	.00		

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

06493 RUBBER KALREZ 1058 GID: DODEXX
MANF: DUPONT

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	2.8E-6	.14	.00	.08	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

84121 RUBBER KALREZ 3018
MANF: DUPONT

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data	B	MECH	414.7	72	-250	0.205	0	20

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.40	.00	.00	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

84229 RUBBER KALREZ 3065
MANF: DUPONT
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006407 3

85388 RUBBER KALREZ 4079 COMPOUND GID: DOXXXX

MANF: DUPONT SPEC: PO R23948

FLAMMABILITY							FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	414.7	72	-250	0.195	0	20

84353 RUBBER KR2001
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84354 RUBBER KR2006
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84355 RUBBER KR2501
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84356 RUBBER KR2502
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84357 RUBBER KR2503
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84358 RUBBER KR2504
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84359 RUBBER KR2601
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84360 RUBBER KR2602
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84361 RUBBER KR2603
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84362 RUBBER KR2604
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84363 RUBBER KR2605
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84364 RUBBER KR2606
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84365 RUBBER KR2621
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006408 5

84366 RUBBER KR2622
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84367 RUBBER KR2623
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84368 RUBBER KR3001
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84369 RUBBER KR3002
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84370 RUBBER KR3003
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84371 RUBBER KR3004
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84372 RUBBER KR3502
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84373 RUBBER KR3503
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84374 RUBBER KR3504
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84375 RUBBER KR3601
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84376 RUBBER KR3602
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84377 RUBBER KR3603
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84378 RUBBER KR3604
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84379 RUBBER KR3605
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006409 7

84380 RUBBER KR3606
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84381 RUBBER KR3621
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84382 RUBBER KR3622
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84383 RUBBER KR3623
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84384 RUBBER KR4002
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84385 RUBBER KR4003
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84386 RUBBER KR4004
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84387 RUBBER KR5002
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84388 RUBBER KR5003
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84389 RUBBER KR5004
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

84390 RUBBER KR9002
MANF: COOK BELTING CO
....NO TEST DATA AVAILABLE....

62385 RUBBER LATEX DENTAL DAM GID: DOXXXX
MANF: HYGENIC CORP

SPEC: ST63R1670-05

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.014		01.00	12.00	T MOD
X	1	025.9	014.3	0.030		00.60	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

ST63R1670-11

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.76	.52	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

80199 RUBBER LATEX DIAMOND CLEAR 11-INCH BALLOON GID: DDXXXX
MANF: PIONEER BALLOON CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	20.794	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006410 3

63018 RUBBER LATEX FAULTLESS GID: DOACXX

MANF: ABBOTT LABS

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	024.5	014.5	0.012		00.14	12.00	T MOD	No test data		No test data							
X	1	024.5	014.5	0.012		01.33	12.00	T MOD										

64023 RUBBER LATEX GLOVES GID: DOACXX

MANF: DAYTON PRODUCTS

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							K	00028.65	

20762 RUBBER LATEX NATURAL GID: DOACXX

MANF: 3D POLYMERS
ABBOTT LABS
FAUTLESS

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	024.5	014.5	0.008		00.18	12.00	T MOD	No test data		No test data							
X	1	024.5	014.5	0.008		01.33	12.00	T MOD										

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	00041.40	

64239 RUBBER MAT

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	00044.40	

83677 RUBBER MBS106

MANF: TRANSENE

....NO TEST DATA AVAILABLE....

83678 RUBBER MBS154

MANF: TRANSENE

....NO TEST DATA AVAILABLE....

83139 RUBBER MONOTHANE A10

MANF: SYNAIR

....NO TEST DATA AVAILABLE....

83140 RUBBER MONOTHANE A100

MANF: SYNAIR

....NO TEST DATA AVAILABLE....

83141 RUBBER MONOTHANE A20

MANF: SYNAIR

....NO TEST DATA AVAILABLE....

83142 RUBBER MONOTHANE A30

MANF: SYNAIR

....NO TEST DATA AVAILABLE....

83143 RUBBER MONOTHANE A40

MANF: SYNAIR

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006411 5

83149 RUBBER MONOTHANE A40HR
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83150 RUBBER MONOTHANE A45SR
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83144 RUBBER MONOTHANE A50
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83145 RUBBER MONOTHANE A60
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83146 RUBBER MONOTHANE A70
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83147 RUBBER MONOTHANE A80
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

83148 RUBBER MONOTHANE A90
MANF: SYNAIR
....NO TEST DATA AVAILABLE....

80250 RUBBER MOSITES 10238 GID: DOXXXX
MANF: MOSITES RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.076			00.10	SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.08	.00	.04	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	21.885	

60098 RUBBER NBR INSULATION GID: DOXXXX
MANF: KIRKHILL RUBBER
SPEC: STW4-2621
....NO TEST DATA AVAILABLE....

05433 RUBBER NEOPRENE GID: DODBXX
MANF: EUTSLER TECHNICAL PROD
FLUID POWER
NASA/JSC
SCOTT AVIATION

SPEC: ASTM D2000
NS-101
ST18N822-02
MIL-R-6855C2TBG80
NS-105BB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.082			01.70	SMALL
A	1	023.8	014.5	0.078			01.70	SMALL
I	2	025.9	014.3	0.079			02.20	NONE
I	2	100.0	019.0	0.079		00.03	05.90	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		77	0.060	2	3
B	PNEU	500		77	0.060	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	8.40	4.66		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00038.90	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006412 7

05623 RUBBER NEOPRENE GID: D0DBXX
MANF: NIKON SPEC: NAS-9-15246
SCOTT AVIATION

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.078			01.50	NONE
C	1	023.8	014.5	0.078		00.15	05.90	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.44	

TOXICITY

20012 RUBBER NEOPRENE GID: DODBXX
MANF: RUBBERCRAFT SPEC: MIL-G-3036

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.069		00.18	12.10	T MOD
X	1	023.8	014.5	0.087		00.23	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		70	0.087	4	24
X	MECH	1500	72	70	0.087	1	02
X	MECH	1500	72	70	0.087	1	2

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	14.10	4.92	.00	

ODOR

RT	RT	WEIGHT	CURE
A	V	00020.30	

TOXICITY

20032 RUBBER NEOPRENE GID: DODBXX
MANF: RUBBERCRAFT SPEC: MIL-R-3065S/SC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	019.0	014.3	0.030			00.80	NONE
A	1	019.0	014.3	0.030			02.70	NONE
X	2	023.8	014.5	0.030			00.80	NONE
X	1	023.8	014.5	0.030		00.41	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00066.21	

TOXICITY

61580 RUBBER NEOPRENE GID: DODBXX
MANF: AQM SPEC: AMS 3208

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.088			00.10	NONE
C	1	020.9	014.7	0.088		00.14	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20005 RUBBER NEOPRENE 60382 GID: DOXXXX
MANF: MOSITES RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.074		00.09	05.90	T SMALL
X	2	020.9	014.7	0.059		00.06	00.20	NONE
X	1	020.9	014.7	0.059		00.30	12.00	T MOD
I	1	025.9	014.3	0.074		00.06	05.90	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61278 RUBBER NEOPRENE BC CWB10 GID: DOXXXX
MANF: CHARLES BRIGHT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	72	-297	0.090	8	25

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006413 9

05837 RUBBER NEOPRENE C147-70 GID: DODBXX
MANF: PARKER SEAL
SPEC: AMS 3209

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.070			00.10	NONE
X	1	025.9	014.3	0.070		00.18	11.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	6.19	1.59		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.04	

05516 RUBBER NEOPRENE C557-70 GID: DODBXX
MANF: PARKER SEAL
SPEC: AMS 3209

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.035		00.37	12.00	T MOD
X	2	023.8	014.5	0.070			00.70	NONE
X	1	023.8	014.5	0.070		00.22	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		250	0.052	2	04
X	MECH	1000	10	250	0.052	0	20
X	PNEU	1000		70	0.067	1	20
X	MECH	1050	15	250	0.065	0	20
X	PNEU	1050		250	0.075	18	100
X	MECH	1050	10	250	0.137	1	02
X	MECH	1050	15	250	0.138	0	20
X	MECH	1050	10	250	0.141	0	20
X	MECH	1500	10	250	0.068	0	20
X	PNEU	1500		70	0.067	2	16
X	MECH	1500	10	70	0.067	0	20
Z	MECH	250	72	70	0.067	2	05
B	PNEU	500		250	0.063	0	20
B	PNEU	500		70	0.067	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.9E-7	22.89	6.77		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05537 RUBBER NEOPRENE CN3 GID: DOXXXX
....NO TEST DATA AVAILABLE....

84020 RUBBER NEOPRENE CR MC
MANF: BOYD INDUSTRY RUBBER
....NO TEST DATA AVAILABLE....

84016 RUBBER NEOPRENE CR45
MANF: BOYD INDUSTRY RUBBER
....NO TEST DATA AVAILABLE....

84017 RUBBER NEOPRENE CR50
MANF: BOYD INDUSTRY RUBBER
....NO TEST DATA AVAILABLE....

84018 RUBBER NEOPRENE CR60
MANF: BOYD INDUSTRY RUBBER
....NO TEST DATA AVAILABLE....

64064 RUBBER NEOPRENE CR70 GID: DODBXX
MANF: APPLE RUBBER INC
BOYD INDUSTRY RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	135	65	250	0.024	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006414 0

05917 RUBBER NEOPRENE E GID: DODBXX
MANF: SPEC: MIL-R-3065
....NO TEST DATA AVAILABLE....

20451 RUBBER NEOPRENE MOUTHPIECE GID: DOHDXX
MANF: SCUBAPRO INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.900		00.59	01.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00017.48	

05795 RUBBER NEOPRENE NCR GID: DODBXX
MANF: SCOTT AVIATION

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	100	10	250	0.031	01	24
X	MECH	100	20	250	0.031	01	06
X	MECH	500	10	250	0.063	2	02
B	PNEU	500		70	0.063	0	20
Z	MECH	65	72	220	0.047	1	24

61146 RUBBER NEOPRENE NS101 GID: DPDBXX
MANF: NASA/JSC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.081			01.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.3E-6	16.14	10.59		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00020.12	

61090 RUBBER NEOPRENE NS105 GID: DODBXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.2E-6	13.23	7.55		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00020.26	

20533 RUBBER NEOPRENE NS105B GID: CHDBXX
MANF: NASA/JSC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.076			01.20	NONE
X	1	033.0	014.3	0.076		00.17	11.80	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.2E-7	12.10	7.25		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00020.43	

61564 RUBBER NEOPRENE NS106 GID: DODBXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.085			01.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60486 RUBBER NEOPRENE NS107 GID: CHDBXX
MANF: NASA/JSC

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006415 2

60486 RUBBER NEOPRENE NS107 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.076			02.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62143 RUBBER NEOPRENE NS111 GID: FIDBXX

MANF: NASA/JSC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00029.49	

62080 RUBBER NEOPRENE NS111B GID: DPDBXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.076			01.20	NONE
X	1	033.0	014.3	0.076		00.14	11.70	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00035.09	

05546 RUBBER NEOPRENE NS6022 GID: DODBXX

MANF: DUPONT

SPEC: ME413-0041

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7				00.30	NONE
B	1	023.8	014.5	0.876			08.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.37	.00	.53	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05836 RUBBER NEOPRENE PRP2337 GID: DOXXXX

MANF: PROD RESEARCH & CHEM

....NO TEST DATA AVAILABLE....

64450 RUBBER NEOPRENE R/C1960 GID: DODBXX

MANF:

SPEC: AMS 3241

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.147			01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61804 RUBBER NEOPRENE SN100 GID: DVDBXX

MANF: NASA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.057		00.09	05.80	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.2E-7	16.57	10.91		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.09	

63020 RUBBER NEOPRENE W180 GID: DODBXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.140			06.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65315 RUBBER NEOPRENE ZX2002 GID: DODBXX

MANF: MINOR RUBBER CO

SPEC: MIL-R-3065

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.077			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006416 4

65315 RUBBER NEOPRENE ZX2002 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	020.9	014.7	0.077		00.10	11.50	T SMALL

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.9E-6	14.35	9.24	.10	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60180 RUBBER NEOPRENE/CARBON FIBER GID: DODGFQ

MANF: SPEC: STW5-2868

....NO TEST DATA AVAILABLE....

20508 RUBBER NEOPRENE/HELMET LINER GID: FGXXXX

MANF: GENTEX CORP
ILC DOVER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	00719.37	

TOXICITY

60174 RUBBER NEOPRENE/SILICONE FILL GID: DOCKXX

MANF: SPEC: STW4-2736

....NO TEST DATA AVAILABLE....

61892 RUBBER NEOTEX ELASTIC GID: BHDBXX

MANF: SCOTT AVIATION SPEC: NAS-9-15246

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.059			01.70	NONE
C	1	023.8	014.5	0.059		00.65	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00020.06	

TOXICITY

05287 RUBBER NITRILE GID: CHDJXX

MANF: PARKER SEAL SPEC: MIL-G-18586C2 MIL-R-3065 TV'S
MIL-STD-417SB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.190		00.01	04.60	MOD
X	1	030.0	010.0	0.190		00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	V 00020.19	

TOXICITY

05345 RUBBER NITRILE GID: DOHDXX

MANF: AQM SPEC: MIL-R-6855C1/2 MIL-R-6855C2G4

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.130		00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	A 00022.61	

TOXICITY

05499 RUBBER NITRILE GID: DOXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.29	3.85	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006417 6

05561 RUBBER NITRILE GID: DOXXXX
SPEC: AMS 3215 MIL-P-18484
MANF:
....NO TEST DATA AVAILABLE....

05619 RUBBER NITRILE GID: DOXXXX
....NO TEST DATA AVAILABLE....

05668 RUBBER NITRILE GID: DODJXX
MANF: SARGENT INDUSTRIES
SPEC: MIL-P-25732

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.031		00.40	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05703 RUBBER NITRILE GID: DPXXXX
SPEC: MIL-P-5516CB
MANF:
....NO TEST DATA AVAILABLE....

20166 RUBBER NITRILE GID: DODJXX
MANF: AQM
....NO TEST DATA AVAILABLE....

20225 RUBBER NITRILE GID: DOXXXX
MANF: GREER HYDRAULICS
....NO TEST DATA AVAILABLE....

61510 RUBBER NITRILE GID: CHDJXX
MANF: SARGENT INDUSTRIES
SPEC: MIL-P-5315B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.591		00.22	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		70	0.059	02	08
X	PNEU	1500		70	0.059	2	08
X	MECH	1500	72	70	0.059	02	08

05204 RUBBER NITRILE (NRB) GID: DODJXX
MANF: WEST AMERICAN RUBBER
SPEC: MIL-P-5510

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	015.0	014.3	0.145		00.06	12.00	T NONE
C	1	017.0	014.3	0.149		00.06	12.00	T SMALL
C	1	019.0	014.3	0.151		0.10	12.00	T SMALL
C	1	023.8	014.5	0.150		00.14	12.00	T SMALL
C	2	030.0	010.0	0.140			00.70	NONE
C	1	030.0	010.0	0.140		00.10	11.70	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.150	01	19
X	PNEU	1500		70	0.150	1	2
X	MECH	1500	20	70	0.150	00	20
B	PNEU	500		70	0.150	00	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.29	3.85	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.04	

61513 RUBBER NITRILE 1070W VIX GID: DODJXX
MANF: E F HOUGHTON & CO
SPEC: MIL-P-5516

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.136			00.80	NONE
B	1	023.8	014.5	0.136		00.05	10.50	NONE
X	1	025.9	014.3	0.132		00.12	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.4E-7	9.64	5.44		

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE
A	00271.38	

61998 RUBBER NITRILE 160 GID: CHDJXX
MANF: GREENE TWEED CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.62	

06193 RUBBER NITRILE 972 GID: DODJXX
MANF: GREENE TWEED CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.079		00.09	07.00	MOD
X	1	030.0	010.0	0.079		0.2	11.70	T MOD

FSC

RT	FLUID NAME
No test data	

XYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	7.0E-6	11.19	6.65	.15	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	21.861	

61512 RUBBER NITRILE CPD 7377 GID: DODJXX
MANF: PRECISION RUBBER SPEC: MIL-P-5516

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.140			00.60	NONE
C	1	023.8	014.5	0.140		00.13	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.3E-7	10.04	5.87		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00019.75	

06198 RUBBER NITRILE FUEL RESISTANT GID: DOXXXX
MANF: SPEC: AMS 7270
....NO TEST DATA AVAILABLE....

84391 RUBBER NITRILE GRADE 30
MANF: COOK BELTING CO SPEC: MIL-R-6855G30
....NO TEST DATA AVAILABLE....

84392 RUBBER NITRILE GRADE 40
MANF: COOK BELTING CO SPEC: MIL-R-6855G40
....NO TEST DATA AVAILABLE....

84236 RUBBER NITRILE GRADE 50
MANF: COOK BELTING CO SPEC: MIL-R-6855G50
....NO TEST DATA AVAILABLI ...

84237 RUBBER NITRILE GRADE 60
MANF: COOK BELTING CO SPEC: MIL-R-6855G60
....NO TEST DATA AVAILABLE....

84238 RUBBER NITRILE GRADE 70
MANF: COOK BELTING CO SPEC: MIL-R-6855G70
....NO TEST DATA AVAILABLE....

84239 RUBBER NITRILE GRADE 80
MANF: COOK BELTING CO SPEC: MIL-R-6855G80
....NO TEST DATA AVAILABLE....

20231 RUBBER NITRILE MS29561-005 GID: DOXXXX
MANF· SPEC: MIL-R-7362
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006419 T

01784 RUBBER NITRILE N304-75 GID: CHDJXX
MANF: PARKER SEAL
SPEC: MIL-D-5516CB MS28775 MIL-P-25732

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.100			01.60	SMALL
C	1	030.0	010.0	0.100		0.1	11.70	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1500	72	70	0.067	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	9.82	6.60	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.28	

06094 RUBBER NITRILE N506-65 GID: DODJXX
MANF: PARKER SEAL
SPEC: AMS 7271

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.095		00.20	11.70	SMALL
X	2	030.0	010.0	0.099		00.09	08.60	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	8.37	2.75	.09	

ODOR

RT
X

TOXICITY

RT	WEIGHT	CURE
A	00020.64	

05002 RUBBER NITRILE N602-7 GID: CHDJXX
MANF: PARKER SEAL
SPEC: MIL-P-5315

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.057		00.21	11.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		70	0.064	2	13
Z	MECH	1500	72	70	0.064	2	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.72	6.02	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00020.10	

65142 RUBBER NITRILE N674-70 GID: DODJXX
MANF: PARKER SEAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.00	2.41	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00022.55	

20236 RUBBER NITRILE N741-75 GID: DODJXX
MANF: PARKER SEAL
....NO TEST DATA AVAILABLE....

06159 RUBBER NITRILE N756-75 GID: DODJXX
MANF: PARKER SEAL
....NO TEST DATA AVAILABLE....

20235 RUBBER NITRILE N766-75 GID: DOXXXX
MANF: PARKER SEAL
SPEC: MIL-P-83461
....NO TEST DATA AVAILABLE....

05794 RUBBER NITRILE NCLS1 GID: DODBXX
MANF: SCOTT AVIATION

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	135		250	0.037	0	40
X	MECH	135	15	250	0.064	0	20
X	MECH	500	72	250	0.068	2	02
B	PNEU	500		500	0.070	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006420 6

05794 RUBBER NITRILE NCLS1 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	500		70	0.070	0	20

05342 RUBBER NITRILE/TFE TEFLON GID: CHDTCN

MANF: GREENE TWEED CO

SPEC: MIL-P-25732

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME
	HYD

MIL-R-8791

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

05767 RUBBER NORDEL EPT75 GID: DOXXXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.075		00.09	06.70	MOD
X	1	030.0	010.0	0.075		0.2	11.70	T LARGE

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	7.0E-6	2.24	.77	.17	

ODOR

RT	RT
A	V

TOXICITY

WEIGHT	CURE
22.399	

60178 RUBBER NYLON REINFORCED GID: DOBSXX

MANF:

SPEC: STW4-2857

....NO TEST DATA AVAILABLE....

69888 RUBBER OUTERWIRE CASING BLACK (PORTION FROM HYDROCARBON SAMPLE LINE) GID: DOXXXX

MANF: NASA/KSC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	8.90	4.66	.26	

ODOR

RT	RT

No test data

TOXICITY

WEIGHT	CURE

84908 RUBBER PELLETHANE 2013-90AEF

MANF: DOW CHEMICAL

....NO TEST DATA AVAILABLE....

84863 RUBBER PELLETHANE 2102-75A

MANF: DOW CHEMICAL

....NO TEST DATA AVAILABLE....

84865 RUBBER PELLETHANE 2102-80A

MANF: DOW CHEMICAL

....NO TEST DATA AVAILABLE....

84867 RUBBER PELLETHANE 2102-80AE

MANF: DOW CHEMICAL

....NO TEST DATA AVAILABLE....

84868 RUBBER PELLETHANE 2102-80PF

MANF: DOW CHEMICAL

....NO TEST DATA AVAILABLE....

84869 RUBBER PELLETHANE 2102-85A

MANF: DOW CHEMICAL

....NO TEST DATA AVAILABLE....

84872 RUBBER PELLETHANE 2102-90A

MANF: DOW CHEMICAL

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006421 8

84874 RUBBER PELLETHANE 2102-90AE
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84877 RUBBER PELLETHANE 2102-90AR
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84878 RUBBER PELLETHANE 2102-90PF
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84880 RUBBER PELLETHANE 2103-70A
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84883 RUBBER PELLETHANE 2103-80A
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84885 RUBBER PELLETHANE 2103-80AE
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84886 RUBBER PELLETHANE 2103-80AEF
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84888 RUBBER PELLETHANE 2103-80AES
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84891 RUBBER PELLETHANE 2103-80PF
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84894 RUBBER PELLETHANE 2103-80WC
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84898 RUBBER PELLETHANE 2103-85AE
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84900 RUBBER PELLETHANE 2103-90A
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84903 RUBBER PELLETHANE 2103-90ACR
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84906 RUBBER PELLETHANE 2103-90AE
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006422 T

Information Handling Services, 2000

84896 RUBBER PELLETHANE 2130-85ACR
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84910 RUBBER PELLETHANE 2202-93A
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84911 RUBBER PELLETHANE 2351-85AE
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84915 RUBBER PELLETHANE 2352-70A
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84916 RUBBER PELLETHANE 2355-75A
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84918 RUBBER PELLETHANE 2355-80A
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84919 RUBBER PELLETHANE 2355-80AE
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84920 RUBBER PELLETHANE 2355-80AEF
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84922 RUBBER PELLETHANE 2355-85ABR
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84923 RUBBER PELLETHANE 2355-90A
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84925 RUBBER PELLETHANE 2355-90AE
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84926 RUBBER PELLETHANE 2355-95ACR
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84927 RUBBER PELLETHANE 2355-95AE
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84928 RUBBER PELLETHANE 2355-95AEF
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006423 1

84930 RUBBER PELLETHANE 2355-95AESP
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84932 RUBBER PELLETHANE 2363-75A
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84934 RUBBER PELLETHANE 2363-80A
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84936 RUBBER PELLETHANE 2363-80AE
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84937 RUBBER PELLETHANE 2363-90A
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

84939 RUBBER PELLETHANE 2363-90AE
MANF: DOW CHEMICAL
....NO TEST DATA AVAILABLE....

62218 RUBBER PHENYL GID: DOBXXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.520			00.20	NONE
A	1	030.0	009.0	0.528			00.10	NONE
A	1	033.0	014.3	0.527			00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	5.1E-6	1.49	.28		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.36	

81672 RUBBER PNF 225-001
MANF: FIRESTONE
....NO TEST DATA AVAILABLE....

81671 RUBBER PNF 240-001
MANF: FIRESTONE
....NO TEST DATA AVAILABLE....

81673 RUBBER PNF 260-004
MANF: FIRESTONE
....NO TEST DATA AVAILABLE....

81674 RUBBER PNF 265-003
MANF: FIRESTONE
....NO TEST DATA AVAILABLE....

81675 RUBBER PNF 265-004
MANF: FIRESTONE
....NO TEST DATA AVAILABLE....

81676 RUBBER PNF 270-001
MANF: FIRESTONE
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006424 3

81677 RUBBER PNF 270-003
MANF: FIRESTONE
....NO TEST DATA AVAILABLE....

62225 RUBBER PNF 270-003R ELASTOMER GID: DOXXXX
MANF: FIRESTONE

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									A	HYZE	No test data							
									A	MMH								
									C	N2O4								

81678 RUBBER PNF 275-006
MANF: FIRESTONE
....NO TEST DATA AVAILABLE....

81679 RUBBER PNF 275-009
MANF: FIRESTONE
....NO TEST DATA AVAILABLE....

81680 RUBBER PNF 280-003
MANF: FIRESTONE
....NO TEST DATA AVAILABLE....

81681 RUBBER PNF 280-008
MANF: FIRESTONE
....NO TEST DATA AVAILABLE....

81682 RUBBER PNF 280-009
MANF: FIRESTONE
....NO TEST DATA AVAILABLE....

81683 RUBBER PNF 285-005
MANF: FIRESTONE
....NO TEST DATA AVAILABLE....

81684 RUBBER PNF 290-003
....NO TEST DATA AVAILABLE....

61923 RUBBER PNF INORGANIC GID: DOXXXX
MANF: FIRESTONE

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									A	HYZE	No test data							
									A	MMH								
									C	N2O4								

61124 RUBBER PNF P39 GID: DODEXX
MANF: NICHOLS ENGINEERING

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		I	MECH	14.7	72	-297	0.080	0	20

60886 RUBBER POLYPHOSPHAZENE (PNF) GID: DOXXXX
MANF: FIRESTONE

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	1000	72	70	0.135	0	20

60886 RUBBER POLYPHOSPHAZENE (PNF) (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72		0.075	00	20
Z	MECH	1500	72		0.135	1	20
I	PNEU	1500		70	0.075	0	2
B	MECH	2000	72	70	0.135	0	20
B	PNEU	2500		70	0.135	0	20
X	PNEU	3000		70	0.135	2	06
X	MECH	5000	20		0.135	0	20
C	MECH	5000	40	70	0.135	0	20

61622 RUBBER POLYURETHANE RUCOTHANE 5154 WITH COTTON FLOC/RED PIGMENT GID: DODUXX

MANF: ILC DOVER SPEC: ST65E1214-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.010		00.20	12.00	T MOD
X	1	025.9	014.3	0.010		00.90	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00019.89	

61620 RUBBER POLYURETHANE RUCOTHANE AX5225 WITH COTTON FLOC GID: DOCQXX

MANF: ILC DOVER SPEC: SK83-02968 SK83-0296B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.015		00.20	12.00	T MOD
X	1	025.9	014.3	0.015		00.60	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.74	

64211 RUBBER POLYURETHANE SORBOTHANE GID: DOXXXX

MANF: HAMILTON KENT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.230			01.10	NONE
X	1	020.9	014.7	0.230		00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.2E-6	15.20	9.71	.35	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00022.28	

64210 RUBBER POLYURETHANE SORBOTHANE/50 GID: DOXXXX

MANF: HAMILTON KENT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.230		00.09	12.00	T MOD
X	1	020.9	014.7	0.230		00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.9E-6	13.94	9.31	.25	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00022.35	

61619 RUBBER POLYURETHANE X364 GID: DODUXX

MANF: ILC DOVER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.010		00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006426 7

61619 RUBBER POLYURETHANE X364 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.010		00.49	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.54	

64983 RUBBER POLYURETHANE X364 RHOPLEX/FLOCC GID: DOCQXX

MANF: ILC DOVER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.020		00.09	12.00	T MOD
X	1	025.9	014.3	0.020		00.68	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.32	

61621 RUBBER POLYURETHANE X364 RUCOTHANE/5154 GID: DOCQXX

MANF: ILC DOVER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.020		00.09	12.00	T MOD
X	1	025.9	014.3	0.020		00.79	12.00	T MOD
X	2	025.9	014.3	0.016		00.16	12.00	T MOD
X	1	025.9	014.3	0.016		00.66	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.48	

85236 RUBBER PUGL40

MANF: POLYMER COMPOSITES

....NO TEST DATA AVAILABLE....

85239 RUBBER PUKV20

MANF: POLYMER COMPOSITES

....NO TEST DATA AVAILABLE....

82504 RUBBER RM630

MANF: RM INDUSTRIAL PRODUCTS

....NO TEST DATA AVAILABLE....

82550 RUBBER RTP 1203-80D

MANF: RTE CORP

....NO TEST DATA AVAILABLE....

82551 RUBBER RTP 1203-90A

MANF: RTE CORP

....NO TEST DATA AVAILABLE....

82553 RUBBER RTP 1299 X 34515B

MANF: RTE CORP

....NO TEST DATA AVAILABLE....

82568 RUBBER RTP 1503-40D

MANF: RTE CORP

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006427 9

82569 RUBBER RTP 1503-55D
MANF: RTE CORP
....NO TEST DATA AVAILABLE....

81816 RUBBER RTV 12C
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81817 RUBBER RTV 12W
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81819 RUBBER RTV 511
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	.94	.23	.00	72H-70F- 48H-257F-0psiaVACUUM	No test data		

65444 RUBBER RTV 577/T-12/SS4415/A276 GID: DOXXXX
MANF: GENERAL ELECTRIC
LORD CORP

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	4.0E-6	2.04	.36	.25	24H-120F-0psia24H-120F VB/21DRT 504H-70F-	No test data		

81820 RUBBER RTV 6157
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81821 RUBBER RTV 627
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81822 RUBBER RTV 660
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81823 RUBBER RTV 662
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81824 RUBBER RTV 668
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81825 RUBBER RTV 670
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	1.37	.65	.00	168H-70F-	No test data		

81826 RUBBER RTV 700 BETA 1
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006428 0

81827 RUBBER RTV 700 BETA 2
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81828 RUBBER RTV 700 BETA 4
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81829 RUBBER RTV 700 BETA 5
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

81830 RUBBER RTV 8262
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.79	.25	.00	18H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60182 RUBBER RTV 88 GID: DOXXXX
MANF: SPEC: STW5-2835

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.66	.36	.00	24H-70F- 24H-275F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62400 RUBBER RUCOTHANE 5154/MS122 GID: DODUXX
MANF: ILC DOVER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	K 00022.18	

TOXICITY

62399 RUBBER RUCOTHANE 5225/MS122 GID: DODUXX
MANF: ILC DOVER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	K 00022.30	

TOXICITY

84990 RUBBER S5370
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.59	.10	.00	72H-302F-0psiaVACUUM

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

69893 RUBBER SANTOPRENE GID: DOXXXX
MANF: MONSANTO SPEC: P/N 990015-0002

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.032			1.125	LARGE
X	2	030.0	010.0	0.060		0.10	12.00 T	LARGE
X	1	030.0	010.0	0.060		0.20	12.00 T	LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	8.87	5.35	.10	

ODOR

RT	RT WEIGHT	CURE
A	K 22.24	

TOXICITY

81831 RUBBER SE5559U
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006429 2

84991 RUBBER SILASTIC 1890
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

06151 RUBBER SILASTIC 35U GID: CHCKXX
MANF: DOW CORNING

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	025.9	014.3	0.099		00.18	05.70	T SMALL	No test data		No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
B	1.0E-6	.14	.06	.00	24H-480F-	A	A	00020.02	

84994 RUBBER SILASTIC 437 BASE
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

20560 RUBBER SILASTIC 55U SILICONE GID: DOCKXX
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

84996 RUBBER SILASTIC 55U/75U
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

84997 RUBBER SILASTIC 590
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

84999 RUBBER SILASTIC 591
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85000 RUBBER SILASTIC 595
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85002 RUBBER SILASTIC 596
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85003 RUBBER SILASTIC 598
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85005 RUBBER SILASTIC 599
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

60511 RUBBER SILASTIC 735 GID: DOCKXX
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85007 RUBBER SILASTIC 745U
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006430 9

85009 RUBBER SILASTIC 746U
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

69937 RUBBER SILASTIC 747
MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	PNEU	2100		77	0.058	00	02
B	PNEU	450		77	0.058	00	20

85011 RUBBER SILASTIC 747U
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85016 RUBBER SILASTIC 75U
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.31	.10	.00	.17H-340F- 3H-399F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

85019 RUBBER SILASTIC 75U/8PPH CAB-O-SIL MS7/DMBPH
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

20778 RUBBER SILASTIC DC55 GID: DOCKXX
MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.032		00.01	06.70	SMALL
C	1	025.9	014.3	0.032		00.20	12.00	T NONE
X	2	025.9	014.3	0.065			02.40	MOD
X	1	025.9	014.3	0.065		00.08	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	1.55	.36		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.26	

TOXICITY

05364 RUBBER SILASTIC DC675 GID: DOCKXX
MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.037		00.03	12.00	T SMALL
C	1	023.8	014.5	0.037		00.22	12.00	T NONE
C	2	030.0	010.0	0.111			00.90	T SMALL
C	1	030.0	010.0	0.111		00.09	11.60	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		200	0.017	1	20
Z	MECH	1000	72	200	0.021	2	13
B	PNEU	1000		200	0.025	0	40
Z	MECH	1000	72	70	0.082	1	3
Z	MECH	1050	10	200	0.067	8	31
X	PNEU	1050		200	0.069	5	62
B	PNEU	1050		70	0.079	0	71
B	PNEU	1050		70	0.079	1	71
X	MECH	1050	15	70	0.079	0	20
B	PNEU	1250		120	0.015	0	20
X	MECH	1250	15	120	0.015	1	17
X	MECH	1250	10	200	0.021	1	1
X	MECH	1250	10	200	0.025	0	14
B	PNEU	1250		70	0.016	0	20
X	MECH	1250	10	70	0.016	1	16

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006431 0

05364 RUBBER SILASTIC DC675 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		200	0.070	1	21
X	MECH	1500	72	70	0.070	1	01
X	MECH	1500	72	70	0.070	1	1
B	PNEU	1500		70	0.079	0	23
X	PNEU	1750		70	0.079	2	21
X	PNEU	2000		200	0.070	4	07
X	PNEU	2000		70	0.079	1	89
Z	MECH	250	72	70	0.070	1	1
X	PNEU	2500		200	0.017	2	08
X	PNEU	2500		70	0.079	1	47
X	PNEU	3000		200	0.017	3	09
X	MECH	3000	72	70	0.082	2	03
X	MECH	3000	72	70	0.082	2	3
X	PNEU	3250		70	0.079	2	29
X	PNEU	3300		200	0.064	9	10
I	MECH	50.0	72	70	0.070	00	20
B	PNEU	500		200	0.017	0	20
Z	MECH	500	72	70	0.082	1	1
X	MECH	5000	5	70	0.070	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.41	.05	.00	.08H-241F- 24H-482F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.26	

63021 RUBBER SILASTIC E RTV SILICONE GID: DODPXX

MANF: RCA

SPEC: Q3-6527 A/B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.5	0.312			02.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.22	.39	.00	168H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

85023 RUBBER SILASTIC FORMULA A

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

85024 RUBBER SILASTIC FORMULA B

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

85025 RUBBER SILASTIC FORMULA C

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

85027 RUBBER SILASTIC FORMULA D

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

85029 RUBBER SILASTIC GP437

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006432 2

85030 RUBBER SILASTIC GP45
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85031 RUBBER SILASTIC GP70
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85032 RUBBER SILASTIC HS
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85033 RUBBER SILASTIC HS30
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85034 RUBBER SILASTIC HS30/HS50
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85035 RUBBER SILASTIC HS50
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85036 RUBBER SILASTIC HS50/HS70
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85037 RUBBER SILASTIC HS70
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85038 RUBBER SILASTIC J
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85039 RUBBER SILASTIC L
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85040 RUBBER SILASTIC LCS740
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85041 RUBBER SILASTIC LS2249U
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85042 RUBBER SILASTIC LS2311U
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85043 RUBBER SILASTIC LS2380U
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

MSFC-HDBK-527 REV F 9999942 0006433 4

Information Handling Services, 2000

85044 RUBBER SILASTIC LS2840
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85045 RUBBER SILASTIC LS2860
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85046 RUBBER SILASTIC LS53U
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85047 RUBBER SILASTIC LS63U
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

61495 RUBBER SILASTIC LT40/RED GID: DODPXX
MANF: DOW CORNING

FLAMMABILITY								FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	PNEU	1500		200	0.014	0	40
											X	PNEU	2000		200	0.030	6	18
											X	PNEU	3300		200	0.014	02	02
											X	MECH	3300	10	200	0.014	2	11
											C	MECH	3300	25	200	0.030	0	20

61494 RUBBER SILASTIC LT40/WHITE GID: DOCKXX
MANF: DOW CORNING

FLAMMABILITY								FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		X	PNEU	1300		200	0.020	3	04
											X	PNEU	1300		200	0.020	3	4
											B	PNEU	1500		200	0.014	0	40
											X	PNEU	1800		200	0.020	4	08
											X	PNEU	2000		200	0.014	6	18
											X	PNEU	2500		200	0.014	3	03
											B	PNEU	300		200	0.020	0	20
											X	PNEU	3000		200	0.014	6	11
											X	PNEU	3000		200	0.014	9	17
											X	PNEU	3300		200	0.014	4	09
											X	MECH	3300	10	200	0.014	02	29
											C	MECH	3300	45	200	0.020	0	20
											X	MECH	3300	10	200	0.030	02	08
											X	PNEU	500		200	0.014	1	05
											B	PNEU	500		200	0.030	0	20
											X	PNEU	800		200	0.020	4	35

85048 RUBBER SILASTIC LT50
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85050 RUBBER SILASTIC NPC40
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85052 RUBBER SILASTIC NPC40/NPC80
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006434 6 ■

85053 RUBBER SILASTIC HPC80
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

05966 RUBBER SILASTIC RTV 731 GID: DODGXX
MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.018	0.003		01.70	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.2E-7	2.05	.99		168H-70F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00051.39	168H-70F-

01811 RUBBER SILASTIC RTV 732 GID: DODGXX
MANF: DOW CORNING SPEC: MIL-A-46106AT1
GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	010.0	0.010			02.20	NONE
A	2	023.8	014.5	0.005	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.005	0.003		01.40	NONE
A	2	023.8	014.5	0.056		00.00	00.00	NONE
A	1	023.8	014.5	0.056			01.40	NONE
A	1	024.5	010.0	0.010			02.20	NONE
A	1	025.9	010.0	0.010			02.20	NONE
A	1	030.0	009.0	0.009	0.003		05.19	NONE
A	1	030.0	010.0	0.010	0.003		03.80	NONE

FSC

RT	FLUID NAME
A	HYZE
A	MMH
C	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.70	.48		24H-70F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00021.68	168H-70F-

61501 RUBBER SILASTIC RTV 732 CL 2 GID: DODPXX
....NO TEST DATA AVAILABLE....

20780 RUBBER SILICONE 'E' GID: DOCKXX
MANF: DOW CORNING SPEC: ST90R1356-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.106			02.50	NONE
C	1	025.9	014.3	0.106		00.11	12.00	T SMALL
I	1	030.0	009.0	0.034		00.23	12.00	T SMALL

FSC

RT	FLUID NAME
A	HYZE
A	MMH
C	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.17	.06	.05	8H-450F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.70	

06256 RUBBER SILICONE 0117 DACRON REINFORCED GID: DVCKCB
MANF: HERCULES SPEC: ZZ-R-765

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.044			05.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05491 RUBBER SILICONE 1000PSI HARDNESS 45 - 55 GID: CHCKXX
MANF: GENERAL ELECTRIC SPEC: AMS 3345

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.036			02.50	NONE
C	1	023.8	014.5	0.036		00.12	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0006435 8

Information Handling Services, 2000

05491 RUBBER SILICONE 1000PSI HARDNESS 45 - 55 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.020		00.21	12.00	T NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.71	.27	.00	24H-250F-0psiaVACUUM

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00071.83	

05872 RUBBER SILICONE 11/T12/RTV9811 GID: DOCKXX

....NO TEST DATA AVAILABLE....

60930 RUBBER SILICONE 11307 GID: CHCKXX

MANF: PRECISION RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.089			00.10	NONE
C	1	025.9	014.3	0.089		00.05	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.4E-6	.24	.05		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.12	

05291 RUBBER SILICONE 1235-70 GID: DODPXX

MANF: PLASTIC & RUBBER CO
SYMETRICS

SPEC: NAS-9-15246

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.065	2	40
Z	MECH	1000	72	70	0.065	01	01
X	PNEU	1050		160	0.068	1	20
X	MECH	1050	10	160	0.068	02	02
X	PNEU	1500		70	0.065	1	14
Z	MECH	1500	72	70	0.065	01	01
Z	MECH	1500	72	70	0.065	02	02
Z	MECH	250	72	70	0.065	02	05
B	PNEU	500		70	0.065	0	20
Z	MECH	500	72	70	0.065	02	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.8E-7	.92	.20		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

80126 RUBBER SILICONE 1258 GID: DOCKXX

MANF: BENTLEY HARRIS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3			0.07	10.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.95	.32	.00	48H-175F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 74.1	

05037 RUBBER SILICONE 14140D GID: DOCKXX

MANF: MOSITES RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.15	.17	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

20638 RUBBER SILICONE 15130

MANF: PLASTIC & RUBBER CO

SPEC: AMS 3332

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006436 T

06395 RUBBER SILICONE 159 GID: DPDPXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.008	0.003		02.10	SMALL
A	1	030.0	009.0	0.011	0.003		01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.37	24H-70F-

80047 RUBBER SILICONE 1671 GID: DOCKXX
MANF: FUJIKURA KASEI

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.020			02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	22.475	

65122 RUBBER SILICONE 200A GID: DOCKXX
MANF: CONN HARD RUBBER
SPEC: AMS 3195

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00022.07	

05807 RUBBER SILICONE 24037 CARBON/FILLED GID: DOCKFD
MANF: DOW CORNING
SPEC: ME413-0038

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.0	014.5	0.500		00.00	00.00	NONE
A	1	030.0	009.0	1.300		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.83	

06579 RUBBER SILICONE 2850R GID: DOCKXX
MANF: MINOR RUBBER CO
SPEC: ZZ-R-765 CL 2A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.248		00.00	00.00	NONE
A	1	030.0	010.4	0.248		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.26	

06258 RUBBER SILICONE 30 SHORE GID: DOCKXX
MANF:
SPEC: AMS 3348
....NO TEST DATA AVAILABLE....

20434 RUBBER SILICONE 382 MEDICAL SI GID: DOCKXX
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

05389 RUBBER SILICONE 388 LB STAGE GID: DOCKXX
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006437 1

20077 RUBBER SILICONE 405 GID: EZXXXX

MANF: DEUTSCH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	023.8	014.5	0.600			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.16	.01	.13	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

62369 RUBBER SILICONE 4216A GID: DOCKXX

MANF: AMERICAN RUBBER CO SPEC: MIL-R-5847

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00008.49	

05427 RUBBER SILICONE 4300 GID: DODPXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.040			00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.3E-6	.19	.02		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00020.15	

05841 RUBBER SILICONE 434 GID: DODPXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.029		00.20	05.80	T NONE
I	1	030.0	009.0	0.029		00.24	05.80	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00020.02	

61333 RUBBER SILICONE 4524 GID: CHCKHD

MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.07	.00		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

20539 RUBBER SILICONE 50 GID: DOCKXX

....NO TEST DATA AVAILABLE....

05440 RUBBER SILICONE 5417-7 GID: DOCKXX

....NO TEST DATA AVAILABLE....

05959 RUBBER SILICONE 555 GID: AZDPXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.030			11.20	NONE
B	1	023.8	014.5	0.030		00.19	12.00	T SMALL
B	1	030.0	009.0	0.030			07.00	SMALL
I	1	030.0	010.0	0.033		00.14	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.76	.53	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00056.87	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006438 3

05611 RUBBER SILICONE 5557 GID: DOCKXX

....NO TEST DATA AVAILABLE....

05643 RUBBER SILICONE 566/NAPTHA SOLV GID: DOCKXX

MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.3E-6	.34	.00		168H-70F- 24H-150F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62188 RUBBER SILICONE 6017 HI DAMP GID: BBCKDA

MANF: BARRY WRIGHT CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.2E-6	.20	.05		24H-250F-0psiaVACUUM

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06085 RUBBER SILICONE 77C 12640 GID: DOCKXX

MANF: BARRY WRIGHT CORP

SPEC: ZZ-R-765

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.267			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.83	.40	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61985 RUBBER SILICONE 89780 GID: DOCKXX

MANF: H O CANFIELD

SPEC: AMS 3304

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.7E-6	.63	.22		

ODOR

RT	RT WEIGHT	CURE
A	K 00043.07	

TOXICITY

05833 RUBBER SILICONE 92276 GID: CHCKXX

MANF: BARRY WRIGHT CORP

SPEC: ZZ-R-765

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.049			00.10	NONE
C	1	023.8	014.5	0.049		00.09	11.60	T SMALL
C	2	023.8	014.5	0.047			00.10	NONE
C	1	023.8	014.5	0.047		00.06	11.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	00.11	00.06	00.00	

ODOR

RT	RT WEIGHT	CURE
A	A 00020.10	

TOXICITY

20199 RUBBER SILICONE 934 HEAT SINK GID: DOCKXX

MANF: SWS SILICONES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.43	.21	.00	168H-70F-

ODOR

RT	RT WEIGHT	CURE
A	B 00020.17	24H-70F- 24H-150F-

TOXICITY

85518 RUBBER SILICONE 950C1569

MANF: KIRKHILL RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.04	.02	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006439 5

85517 RUBBER SILICONE 950C1569 TOX RATE STUDY
MANF: KIRKHILL RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
S		

05880 RUBBER SILICONE AP3004 CL 3A GR 50 GID: DOCKXX
MANF: ARROWHEAD PRODUCTS SPEC: ZZ-R-765 CL 3A GR 50

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.080			03.50	NONE
X	1	023.8	014.5	0.087			06.90	MOD
C	1	023.8	014.5	0.080		00.07	12.00	T SMALL
B	1	025.9	014.3				06.50	SMALL
X	2	025.9	014.3	0.181		00.00	00.00	NONE
X	1	025.9	014.3	0.181		00.01	06.70	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	.35	.18	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00134.63	

69936 RUBBER SILICONE BMS 1-70 GR 40
MANF: BOEING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.110			03.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	6.0E-6	.09	.00	.03	16H-480F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	22.732	16H-480F-

06016 RUBBER SILICONE BTR GID: DOCKXX
MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.135			03.00	NONE
I	1	033.0	014.3	0.135			07.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	7.9E-6	.37	.07		24H-250F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00019.84	

05811 RUBBER SILICONE C6-1103 GID: DOCKXX
....NO TEST DATA AVAILABLE....

05689 RUBBER SILICONE CHOSEAL 1212 GID: DOCKXX
MANF: CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.060			01.30	NONE
C	1	023.8	014.5	0.060		00.09	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.09	.03	.00	4H-194F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00326.16	

05573 RUBBER SILICONE CHOSEAL 1215 GID: DVCKXX
MANF: CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.068		00.58	05.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006440 1

05573 RUBBER SILICONE CHOSEAL 1215 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.15	.07	.13	1H-338F-

ODOR

RT	RT WEIGHT	CURE
A	V 00019.85	

TOXICITY

84144 RUBBER SILICONE CHOSEAL 1220

MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.34	.08	.00	.25H-340F- 3H-351F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05753 RUBBER SILICONE CHOSEAL 1224 GID: ABCKXX

MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.43	.07	.00	.25H-340F- 3H-351F-

ODOR

RT	RT WEIGHT	CURE
	K 00020.12	

TOXICITY

62000 RUBBER SILICONE CHOSEAL 1285 GID: CHCKMR

MANF: CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.125		00.17	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.12	.05	.00	24H-350F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

84151 RUBBER SILICONE CHOSEAL 1287

MANF: CHOMERICS

....NO TEST DATA AVAILABLE....

84152 RUBBER SILICONE CHOSEAL 1350

MANF: CHOMERICS

....NO TEST DATA AVAILABLE....

84154 RUBBER SILICONE CHOSEAL 1401

MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.06	.03	.00	24H-351F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

84155 RUBBER SILICONE CHOSEAL 1485

MANF: CHOMERICS

....NO TEST DATA AVAILABLE....

84157 RUBBER SILICONE CHOTHERM 1641

MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.58	.09	.00	24H-46F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

84158 RUBBER SILICONE CHOTHERM 1642

MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.44	.18	.00	SEE TEST REPORT

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006441 3

05683 RUBBER SILICONE CHOTHERM 1661 GID: CHDPXX

MANF: CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.023			01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.2E-7	.28	.10		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00043.22	

63017 RUBBER SILICONE CHOTHERM 1661 WITH CHOBOND 320 GID: DOCKXX

MANF: CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.025			03.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05171 RUBBER SILICONE CHOTHERM 1663

MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.53	.14	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00025.88	

05595 RUBBER SILICONE CHOTHERM 1664 GID: DUCKXX

MANF: CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.008		00.16	08.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.45	.13	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00019.53	

84159 RUBBER SILICONE CHOTHERM 1665

MANF: CHOMERICS

....NO TEST DATA AVAILABLE....

84160 RUBBER SILICONE CHOTHERM 1666

MANF: CHOMERICS

....NO TEST DATA AVAILABLE....

84161 RUBBER SILICONE CHOTHERM 1667

MANF: CHOMERICS

....NO TEST DATA AVAILABLE....

64178 RUBBER SILICONE CHOTHERM 1671 GID: DOCKXX

MANF: CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.015			02.40	NONE
A	1	025.9	014.3	0.015			03.60	NONE
A	1	030.0	010.0	0.016			02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.05	.00		24H-350F-0psia10E-2 TORR

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	9.96	

06535 RUBBER SILICONE CHOTHERM 1673R GID: DOCKXX

MANF: CHOMERICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.11	.04	.00	24H-347F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006442 5 ■

63043 RUBBER SILICONE CL 1A & 1B GR 40 GID: DODPXX

MANF: ROCKWELL — SPEC: ZZ-R-765 CL 1A & 1B GR 40

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.250			00.10	NONE	No test data		No test data					

64807 RUBBER SILICONE CL 1A & 1B GR 50 GID: OBVBG

MANF: TULSA DIV — SPEC: ZZ-R-765 CL 1A & 1B GR 50

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	020.9	014.7	0.032		00.06	12.00	T MOD	No test data		No test data					
I	1	024.5	014.3	0.047		00.03	06.00	T NONE								
A	2	025.9	014.3	0.104			00.10	NONE								
A	1	025.9	014.3	0.104			07.10	NONE								
X	2	025.9	014.3	0.032			06.30	MOD								

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	.58	.19	.02	

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	K	00020.51	

84240 RUBBER SILICONE CL 1A & 1B GR 60

MANF: — SPEC: ZZ-R-765 CL 1A & 1B GR 60

....NO TEST DATA AVAILABLE....

84241 RUBBER SILICONE CL 1A & 1B GR 70

MANF: — SPEC: ZZ-R-765 CL 1A & 1B GR 70

....NO TEST DATA AVAILABLE....

05147 RUBBER SILICONE CL 1A & 1B GR 80 GID: DVDPXX

MANF: KIRKHILL RUBBER — SPEC: P/N 980-N-702 ZZ-R-765 CL 1B GR 80

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	030.0	009.0	0.086			02.30	SMALL	No test data		No test data					

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.15	.02	.00	

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	B	00175.91	16H-480F-

05288 RUBBER SILICONE CL 2A & 2B GR 25 GID: CHCKCD

MANF: — SPEC: ZZ-R-765 CL 2A & 2B GR 25

....NO TEST DATA AVAILABLE....

05729 RUBBER SILICONE CL 2A & 2B GR 40 GID: BDCKIA

MANF: — SPEC: ZZ-R-765 CL 2A & 2B GR 40

....NO TEST DATA AVAILABLE....

05394 RUBBER SILICONE CL 2A & 2B GR 50 GID: CHCKBV

MANF: — SPEC: ZZ-R-765 CL 2A & 2B GR 50

....NO TEST DATA AVAILABLE....

05149 RUBBER SILICONE CL 2A & 2B GR 60 GID: CHCKXX

MANF: KIRKHILL RUBBER — SPEC: P/N 960-C-1778 ZZ-R-765 CL 2B GR 60

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	2	023.8	014.5	0.014			09.80	MOD	No test data		No test data					
X	1	023.8	014.5	0.014		00.27	12.00	T NONE								

60126 RUBBER SILICONE CL 2A & 2B GR 70 GID: DOCKXX

MANF: AQM — SPEC: ZZ-R-765 CL 2B

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006443 7

05376 RUBBER SILICONE CL 2A & 2B GR 80 GID: CHCKCO
MANF: SPEC: ZZ-R-765 CL 2A & 2B GR 80
....NO TEST DATA AVAILABLE....

60851 RUBBER SILICONE CL 3A GR 25 GID: DODPXX
MANF: ACE RUBBER CO SPEC: P/N 10-250 ZZ-R-765 CL 3A GR 25

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.6E-6	.53	.41		16H-400F-

ODOR

RT	RT WEIGHT	CURE
A	B 00116.79	16H-400F-

TOXICITY

05272 RUBBER SILICONE CL 3A GR 30 GID: CHCKBV
MANF: SPEC: ZZ-R-765 CL 3A GR 30

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.7	0.125			02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85512 RUBBER SILICONE CL 3A GR 60
MANF: SPEC: ZZ-R-765 CL 3A GR 60
....NO TEST DATA AVAILABLE....

60847 RUBBER SILICONE CL 3B GR 30 GID: DODPXX
MANF: ACE RUBBER CO SPEC: P/N 10-256 ZZ-R-765 CL 3B GR 30

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.125			01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.6E-6	.82	.37		16H-400F-

ODOR

RT	RT WEIGHT	CURE
A	B 00113.76	16H-400F-

TOXICITY

05148 RUBBER SILICONE CL 3B GR 50 GID: DODPXX
MANF: A B BOYD SPEC: ZZ-R-765 CL 3B GR 50
KIRKHILL RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.130			02.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.22	.09	.00	4H-399F-

ODOR

RT	RT WEIGHT	CURE
A	B 00133.04	4H-400F-

TOXICITY

85514 RUBBER SILICONE CL 3B GR 60
MANF: SPEC: ZZ-R-765 CL 3B GR 60
....NO TEST DATA AVAILABLE....

85509 RUBBER SILICONE CL 3B GR 70
MANF: FLUID POWER INC SPEC: ZZ-R-765 CL 3B GR 70
....NO TEST DATA AVAILABLE....

85516 RUBBER SILICONE CL 3B GR 80
MANF: SPEC: ZZ-R-765 CL 3B GR 80
....NO TEST DATA AVAILABLE....

60620 RUBBER SILICONE CP6007 GID: AZCKXX
MANF: BARRY WRIGHT CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.09	.36	.00	.25H-289F-
					4H-291F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006444 9

65141 RUBBER SILICONE CV1144-0 GID: AKCKXX
MANF: MCGHAN NUSIL SPEC: LAC37-4777-0100 P/N 40-9570100050

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.011	0.003	00.09	03.75	NONE
A	1	030.0	010.0	0.002	0.003		01.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64322 RUBBER SILICONE CV2500 GID: DOXXXX
MANF: GENERAL ELECTRIC
MCGHAN NUSIL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7				05.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.33	.07	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

69800 RUBBER SILICONE CV2942 GID: ABCKXX
MANF: MCGHAN NUSIL SPEC: LAC40-4730B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.024		11.3	00.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.10	.05	.02	1H-70F-12.4psia 4H-150F-12.4psia

ODOR

RT	RT	WEIGHT	CURE
	K	22.542	

TOXICITY

62556 RUBBER SILICONE D173-100-12 GID: DODPXX
MANF: UNITED STATES RADIUM

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.4E-6	1.74	.78		

ODOR

RT	RT	WEIGHT	CURE
A	V	00000.01	

TOXICITY

05426 RUBBER SILICONE DC CF217U GID: DOCKXX
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

63200 RUBBER SILICONE DC Q3-6567 A/B GID: DODPXX
MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.097	0.001		01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.67	.20	.00	3H-176F-

ODOR

RT	RT	WEIGHT	CURE
	B	00034.20	12H-70F- 3H-176F-

TOXICITY

05418 RUBBER SILICONE DC8-2318U GID: DOCKXX
MANF: DOW CORNING SPEC: MIL-M-27274

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.265			03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		70	.126	2	04
X	PNEU	1500		70	0.126	2	04

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.7E-6	.70	.28		

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.10	

TOXICITY

MSFC-HDBK-527 REV F 9999942 0006445 0

05824 RUBBER SILICONE DC90-006 GID: DOCKXX
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.23	.32	.00	24H-158F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

02638 RUBBER SILICONE DC93-072 GID: DOCKXX
MANF: DOW CORNING
SPEC: MB0130-102

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	1.90	1.02	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06467 RUBBER SILICONE DC93-076 GID: DOCKXX
MANF: DOW CORNING
SPEC: 10A00526 P2.0 10A00527
10A00527 P2.0 MB0130-107T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.125	0.125	00.00	00.00	NONE
C	2	023.8	014.5	0.008	0.003	00.04	12.00 T	SMALL
C	1	023.8	014.5	0.008	0.003	00.14	12.00 T	NONE
C	2	025.9	014.3	0.140			00.50	NONE
C	1	025.9	014.3	0.140		00.06	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.30	.96	.00	16H-70F- 16H-104F- 4H-140F- 4H-300F-

ODOR

RT	RT WEIGHT	CURE
A	B 00020.31	168H-70F-

TOXICITY

61846 RUBBER SILICONE DC93-500 GID: DODPXX
MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.060		03.06	10.70 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.11	.00	.08	24H-392F- 168H-46F- 4H-140F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65381 RUBBER SILICONE DIMETHYL SILOXANE GID: DOCKXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	K 00026.36	

TOXICITY

20066 RUBBER SILICONE DMCPS1008 GID: DOCKXX
MANF: DEUTSCH
....NO TEST DATA AVAILABLE....

63044 RUBBER SILICONE DURO 40 GID: DODPXX
MANF: KIRKHILL RUBBER
SPEC: MIL-R-5847C2A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.3	0.032		00.01	09.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63494 RUBBER SILICONE DURO 70 GID: DOCKXX
MANF: KIRKHILL RUBBER

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006446 2

63494 RUBBER SILICONE DURO 70 (cont)

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1-	030.0	010.0	0.090		00.09	12.00	T SMALL	No test data	No test data							

06257 RUBBER SILICONE E2022A HI-DAMP GID: DOCKXX
MANF: BARRY WRIGHT CORP

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.0E-6	.83	.48			No test data		

05519 RUBBER SILICONE E2024/20412038 GID: DOCKXX
....NO TEST DATA AVAILABLE....

05589 RUBBER SILICONE E2038 HI-DAMP GID: DVDPXX
MANF: BARRY WRIGHT CORP SPEC: MB0125-075

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	8.4E-7	.29	.10			No test data		

05588 RUBBER SILICONE E2041 HI-DAMP GID: DVDPXX
MANF: BARRY WRIGHT CORP SPEC: MB0125-075

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data						A	A 00117.42	

06101 RUBBER SILICONE E2053 HI DAMP GID: DVDPXX
....NO TEST DATA AVAILABLE....

65075 RUBBER SILICONE E6132 GID: CHCKXX
MANF: EUTSLER TECHNICAL PROD SPEC: ASTM D2000

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	030.0	010.0	0.500			03.00	NONE	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data							K 00021.25	

00155 RUBBER SILICONE EMS342 GID: DOCKXX
MANF: AIRESEARCH
....NO TEST DATA AVAILABLE....

05422 RUBBER SILICONE EMS9300 GID: DOCKXX
MANF: AIRESEARCH
....NO TEST DATA AVAILABLE....

20121 RUBBER SILICONE EXTREME LOW TEMPERATURE LOW TEMPERATURE HARDNESS SHORE "A" 65-75 GID: DOCKXX
MANF: AIRCRAFT SEAL SPEC: AMS 3303
JBL CORP
RUBBERCRAFT

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	2	020.9	014.7	0.060			00.10	NONE	No test data	No test data							
B	1	020.9	014.7	0.060			07.90	NONE									
I	1	023.8	014.5	0.013		00.50	11.60	T NONE									
I	1	030.0	009.0	0.023		00.24	12.00	T NONE									

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.21	.04	.00		A	A 00020.62	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006447 4

60616 RUBBER SILICONE FMS510 GID: DOCKXX

MANF: FLUOROCARBON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.080		00.08	05.80	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.82	

06145 RUBBER SILICONE FUEL/OIL RESIS GID: DOCKXX

....NO TEST DATA AVAILABLE....

05711 RUBBER SILICONE GR 2 GID: DODPXX

MANF: BUCKEYE RUBBER

SPEC: ASTM D-2000

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.062		00.24	11.70	T SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.4E-6	12.16	7.08		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00010.00	

60605 RUBBER SILICONE GROENDYK 7504 GID: DODPXX

MANF: GROENDYK

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.20	

60852 RUBBER SILICONE H567 GID: DODPXX

MANF: HERCULES

SPEC: ZZ-R-765 CL 3B

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.6E-7	.08	.03		16H-400F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00095.26	16H-400F-

60848 RUBBER SILICONE HADBAR 3250 GID: DODPXX

MANF: HADBAR

SPEC: ZZ-R-765 CL 3B GR 25

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.6E-7	.21	.09		16H-400F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00108.77	16H-400F-

60849 RUBBER SILICONE HADBAR 3254 GID: DODPXX

MANF: HADBAR

SPEC: ZZ-R-765 CL 3A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.3E-6	.22	.06		16H-400F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00110.08	16H-400F-

05461 RUBBER SILICONE HARDNESS SHORE "A" 35-45 GID: CHCKXX

MANF: AEROSTAT
CONN HARD RUBBER

SPEC: AMS 3301

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.040			00.10	NONE
C	1	023.8	014.5	0.040		00.11	12.00	T NONE
X	2	023.8	014.5	0.100			01.10	MOD
X	1	023.8	014.5	0.100		00.16	12.00	T MOD
C	2	030.0	010.0	0.060			01.80	NONE
C	1	030.0	010.0	0.060		00.09	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.8E-7	1.00	.44		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00010.01	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006448 6

05571 RUBBER SILICONE HARDNESS SHORE "A" 45-55 GID: DOCKXX

MANF: DUPONT SPEC: AMS 3302D

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	023.8	014.5	0.061		00.07	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.7E-6	.20	.03		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00108.50	

05142 RUBBER SILICONE HARDNESS SHORE "A" 55-65 GID: DOCKXX

MANF: BOYD INDUS RUBBER SPEC: AMS 3301 AMS 3303
HADBAR AMS 3337
KIRKHILL RUBBER
RUBBERCRAFT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.060			01.90	T SMALL
C	1	023.8	014.5	0.060		00.12	12.00	T SMALL
X	2	023.8	014.5	0.024		00.02	12.00	T MOD
X	1	023.8	014.5	0.024		00.22	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.8E-7	1.37	.25		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.49	

05344 RUBBER SILICONE HARDNESS SHORE "A" 65-75 GID: DVDDXX

MANF: PLASTIC & RUBBER CO SPEC: AMS 3304

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
V	00028.31	

05390 RUBBER SILICONE HB400-50 GID: DOCKXX

MANF: HADBAR

....NO TEST DATA AVAILABLE....

60850 RUBBER SILICONE HERCULES H564 GID: DODPXX

MANF: HERCULES SPEC: ZZ-R-765 CL 3A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.6E-7	.22	.12		16H-400F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00091.97	16H-400F-

63502 RUBBER SILICONE HT 2-80 SHOCK ISOLATOR GID: DOXXXX

MANF: LORD CORP SPEC: AMS 3301 ZZ-R-765
SEE TEST REPORT
W18161

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.8E-6	.65	.22	.19	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

60586 RUBBER SILICONE K1203 GID: DODPXX

MANF: UNION CARBIDE

....NO TEST DATA AVAILABLE....

80046 RUBBER SILICONE KE941U GID: DOCKXX

MANF: SHIN-ETSU CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	024.5	014.5	0.060		0.001	01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006449 8

80046 RUBBER SILICONE KE941U (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.060		0.1	11.90	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	22.591	

65448 RUBBER SILICONE MDX4-4210 MEDICAL GRADE GID: DOCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.178			05.50	T SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00053.26	24H-70F-

60474 RUBBER SILICONE MEDICAL GRADE GID: DOCKXX

MANF: DOW CORNING

SPEC: ST925621-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.021		00.31	08.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.2E-7	.12	.00		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00006.25	

06144 RUBBER SILICONE NE6016 GID: DOCKXX

....NO TEST DATA AVAILABLE....

20404 RUBBER SILICONE NE6070 GID: DODPXX

MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.125			00.10	NONE
C	1	025.9	014.3	0.125		00.03	12.00	T SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	8.0E-7	.08	.00		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00023.31	

06147 RUBBER SILICONE NE6071/6071 GID: CHCKXX

MANF: LORD CORP
NICHOLS ENGINEERING

SPEC: AMS 3327 AMS 3377
ZZ-R-765 CL 2B GR 80

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.112			00.20	NONE
C	1	025.9	014.3	0.112		00.05	11.90	T NONE
X	2	025.9	014.3	0.137			00.10	NONE
X	1	025.9	014.3	0.137		00.05	12.00	T MOD
I		100.0	019.0					NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.9E-6	1.07	.07		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.072	1	12
X	MECH	1050	15	70	0.080	0	20
X	PNEU	1500		70	0.072	2	11
I	PNEU	750		70	0.072	0	10

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.19	

06155 RUBBER SILICONE NE687B/5687 GID: DPHDCK

MANF: LORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.125			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006450 4

06155 RUBBER SILICONE HE687B/5687 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B.	1	025.9	014.3	0.125			09.70	SMALL

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	1.03	.33		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
V	00020.10	

05762 RUBBER SILICONE NICKEL FILLED ADHESIVE GID: DOCKXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.004	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	.79	.16	.05	336H-70F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

06208 RUBBER SILICONE NOC GID: DOCKXX

....NO TEST DATA AVAILABLE....

60211 RUBBER SILICONE NOC GID: DOCKXX

MANF: RAYCHEM
RUBATEX
SARGENT INDUSTRIES

SPEC: EH32 (82-150) RB0130-040 T2
RB0130-091 T1 RB0130-091 T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.125			02.70	MOD
A	1	020.9	014.7	0.062			00.10	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.36	.21	.00	24H-320F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00033.65	

02976 RUBBER SILICONE NOC ZZ-R-765 GID: DOCKXX

MANF: BOYD INDUS RUBBER
CHASE TECHNOLOGY
CONN HARD RUBBER
PARKER SEAL

SPEC: MS27511C10C ZZ-R-765

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.015		00.28	12.00 T	NONE
B	2	025.9	014.3	0.104			00.10	SMALL
B	1	025.9	014.3	0.104			07.10	SMALL
B	1	025.9	014.3	0.125			06.40	NONE
X	1	030.0	009.0	0.125		00.02	12.00 T	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		70	0.020	02	04

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.08	.00	.00	24H-446F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

06286 RUBBER SILICONE O-RINGS GID: DOCKXX

MANF: GENERAL ELECTRIC
J ROYAL CO
PARKER SEAL
ZEISS

SPEC: AMS 3304 AMS 3325
MS9068-014 P/N 2-014-5604-70

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7			00.06	12.00 T	SMALL
C	2	025.9	014.3	0.014		00.00	00.00	NONE
C	1	025.9	014.3	0.014		00.05	12.00 T	NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006451 6

06286 RUBBER SILICONE O-RINGS (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.140			00.10	NONE
X	1	025.9	014.3	0.140		00.03	11.90	T MOD
X	2	100.0	020.2	0.014		00.13	12.00	T MOD
X	1	100.0	020.2	0.014		00.32	12.00	T MOD
X	2	100.0	020.2	0.140		00.15	12.00	T MOD
X	1	100.0	020.2	0.140		00.31	11.90	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.16	.33	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00024.40	

63032 RUBBER SILICONE ON AL/SILASTIC E GID: ABDPXX

MANF: DOW CORNING
KIRKHILL RUBBER

SPEC: MMS-C-132A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.125	0.063	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60477 RUBBER SILICONE PARCO 1235-70 GID: DOCKXX

MANF: PLASTIC & RUBBER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	1050	15	160	0.065	2	09
X	PNEU	1050		160	0.066	16	111
X	MECH	1050	15	160	0.071	2	07
X	MECH	1050	10	160	0.072	0	20
X	PNEU	1250		160	0.066	8	79
X	MECH	1250	10	160	0.066	0	20
X	PNEU	1250		160	0.069	8	79

61509 RUBBER SILICONE PRE100-40R GID: DOCKXX

MANF: PLASTIC & RUBBER CO

SPEC: AMS 3301

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.016			09.90	MOD
X	1	023.8	014.5	0.016		00.25	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00031.91	

05746 RUBBER SILICONE PRP11207 GID: DOCKXX

MANF: PRECISION RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.075		00.27	05.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	2.09	.24		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00020.48	

06274 RUBBER SILICONE PRP11307 GID: DOCKXX

....NO TEST DATA AVAILABLE....

60512 RUBBER SILICONE R425 GID: DOCKXX

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006452 8

63027 RUBBER SILICONE RA-5211U GID: DOCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.125			02.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00049.00	4H-450F-

63026 RUBBER SILICONE RA38140 GID: DODPXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.125			02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06156 RUBBER SILICONE REDAR S59-808 GID: DOCKXX

....NO TEST DATA AVAILABLE....

62459 RUBBER SILICONE RTV 1/SILVER GID: DOCKMR

MANF: TECKNIT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.025			01.90	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.05	.02	.00	24H-351F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00036.57	24H-70F-

05310 RUBBER SILICONE RTV 1016/9910 GID: DOCKXX

....NO TEST DATA AVAILABLE....

00128 RUBBER SILICONE RTV 102 GID: DOCKXX

MANF: GENERAL ELECTRIC

SPEC: MB0120-041

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.008	0.003		01.40	NONE
I	1	030.0	010.0	0.061		00.02	12.00	T SMALL
A	1	033.0	014.3	0.008	0.003		01.80	NONE
X	2	100.0	019.0	0.008	0.003	00.48	12.00	T NONE
X	1	100.0	019.0	0.008	0.003	02.03	12.00	T NONE

FSC

RT	FLUID NAME
A	HYZE
A	MMH
X	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	40		70	0.007	0	20
I	MECH	40	72	70	0.007	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.45	1.63	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00021.07	24H-70F-
		24H-150F-

62006 RUBBER SILICONE RTV 103 GID: DOCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE
A	MMH
C	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.35	1.72	.00	24H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

06191 RUBBER SILICONE RTV 106 GID: DOCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.3	0.011	0.003		02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006453 T

06191 RUBBER SILICONE RTV 106 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.3	0.011	0.003		02.30	SMALL
A	1	024.5	014.3	0.011	0.003		02.30	SMALL
A	1	025.9	014.3	0.011	0.003		02.30	SMALL
A	1	030.0	014.3	0.011	0.003		03.50	SMALL
A	1	033.0	014.3	0.011	0.003		03.50	SMALL
I	1	100.0	020.2	0.025	0.003	00.96	12.00 T	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	8.2E-7	2.11	1.04		24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00023.71	24H-70F- 24H-150F-

05771 RUBBER SILICONE RTV 108 GID: DPDRXX

MANF: GENERAL ELECTRIC

SPEC: MIL-A-46106

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	010.0	0.010			02.10	NONE
A	1	023.8	010.0	0.010			02.10	NONE
A	1	024.5	010.0	0.010			02.10	NONE
X	1	025.9	014.3	0.018	0.003		04.80	MOD
A	1	025.9	010.0	0.010	0.003		02.10	NONE
A	1	030.0	010.0	0.010			02.10	NONE
X	1	033.0	014.3	0.018	0.003		02.70	MOD
X	2	100.0	019.0	0.018	0.003	00.38	12.00 T	NONE
X	1	100.0	019.0	0.018	0.003	00.94	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	250		70	0.137	0	20
Z	MECH	250	72	70	0.137	02	02
B	PNEU	40		70	0.007	0	20
Z	MECH	40	72	70	0.007	02	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.52	1.60	.00	24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.31	168H-70F- 24H-150F-

05924 RUBBER SILICONE RTV 112 GID: DOCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.012	0.003		00.90	NONE
A	1	020.9	014.7	0.012	0.003		01.40	SMALL
C	2	030.0	010.0	0.080		00.07	02.60	NONE
C	1	030.0	010.0	0.080		00.11	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05800 RUBBER SILICONE RTV 116 GID: ABCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.007	0.003		01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.4E-7	1.92	.89		24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.74	24H-70F- 24H-150F-

05742 RUBBER SILICONE RTV 118 GID: DPCKGL

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.087	0.003		00.40	NONE
I	1	030.0	010.0	0.060		00.20	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006454 1

05742 RUBBER SILICONE RTV 118 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	2.21	1.07	.00	24H-70F-

ODOR

RT	RT	WEIGHT	CURE
	B	00295.12	24H-70F-

TOXICITY

62392 RUBBER SILICONE RTV 12 A/B GID: DODPXX

MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.9E-6	1.16	.45	.00	3H-150F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60253 RUBBER SILICONE RTV 133 GID: DOXXXX

MANF: GENERAL ELECTRIC

....NO TEST DATA AVAILABLE....

20155 RUBBER SILICONE RTV 140 GID: ABCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.133		00.05	11.90	T MOD

FSC

RT	FLUID NAME
A	HYD
A	MMH
C	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.73	.01	.00	24H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00020.16	48H-70F-
			48H-150F-

TOXICITY

05680 RUBBER SILICONE RTV 142 GID: DOCKXX

MANF: GENERAL ELECTRIC

SPEC: MB0130-144

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.003			02.50	NONE
A	1	025.9	014.3	0.003			03.00	NONE
A	1	030.0	010.0	0.009			01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.21	.01	.00	144H-70F-

ODOR

RT	RT	WEIGHT	CURE
	A	00086.49	

TOXICITY

20396 RUBBER SILICONE RTV 156 GID: DODPXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.019	0.003		01.50	SMALL
A	1	033.0	014.3	0.020	0.003		02.50	SMALL
X	1	100.0	020.2	0.020	0.003	01.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	6.0E-7	2.22	.95		24H-70F-
					24H-150F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00024.42	24H-70F-
			24H-150F-

TOXICITY

05185 RUBBER SILICONE RTV 162 GID: DOCKXX

MANF: GENERAL ELECTRIC

SPEC: MIL-A-46106 MIL-A-46146

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.013	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.013	0.003		01.80	NONE
A	1	024.5	014.5	0.010	0.005		05.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006455 3

05185 RUBBER SILICONE RTV 162 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.013	0.003		04.00	NONE
I	1	030.0	010.0	0.115		00.10	12.00	T NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.53	.36	.00	168H-70F- 24H-150F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00024.03	168H-70F- 24H-150F-

TOXICITY

05184 RUBBER SILICONE RTV 168 GID: DOCKXX

MANF: GENERAL ELECTRIC SPEC: MIL-A-46146

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.72	.56	.00	24H-170F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05693 RUBBER SILICONE RTV 21 GID: DOCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.021	0.003		02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.6E-6	1.15	.27		168H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

61984 RUBBER SILICONE RTV 2318 GID: CHDPXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.128			04.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70	0.100	0	20
Z	MECH	1000	35	70	0.100	02	12

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	V	00020.05	

TOXICITY

61506 RUBBER SILICONE RTV 281-400S GID: DOCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.014	0.003		01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.4E-6	.28	.01		168H-70F- 24H-150F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

63031 RUBBER SILICONE RTV 282 ADHESIVE GID: DODPXX

MANF: DOW CORNING
KIRKHILL RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.125	0.062	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62005 RUBBER SILICONE RTV 30-121 GID: DOCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006456 5

62005 RUBBER SILICONE RTV 30-121 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME
A	MMH
C	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

05361 RUBBER SILICONE RTV 3110 GID: BACKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.090			01.40	MOD
X	1	023.8	014.5	0.090		00.07	12.00 T	MOD
X	2	030.0	010.0	0.090		00.01	02.10	NONE
X	1	030.0	010.0	0.090		00.05	08.25	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.85	.25		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62307 RUBBER SILICONE RTV 3112 GID: DOCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.3	0.060		00.05	11.90 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1000	72	70	0.065	01	02
I	MECH	14.7	72	70	0.095	0	20
Z	MECH	150	72	70	0.065	02	07
Z	MECH	1500	72	70	0.065	01	02
B	PNEU	2000		70	0.065	0	20
Z	MECH	2000	72	70	0.065	01	01
Z	MECH	250	72	70	0.065	01	01
X	PNEU	2500		70	0.065	2	06
X	PNEU	3000		70	0.065	2	09
X	PNEU	4000		70	0.065	2	04
Z	MECH	500	72	70	0.065	01	01
X	PNEU	5000		70	0.065	2	04
X	PNEU	6000		70	0.065	1	02

06489 RUBBER SILICONE RTV 3112/CATALYST F GID: DOCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.120			00.60	NONE
X	1	025.9	014.3	0.119			06.40	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.91	.24	.00	24H-46F-

ODOR

RT	RT WEIGHT	CURE
A	B 00020.28	72H-70F-

TOXICITY

05532 RUBBER SILICONE RTV 3116 GID: DPCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.008	0.003		03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.47	.48	.00	4H-151F-

ODOR

RT	RT WEIGHT	CURE
A	B 00041.98	12H-70F- 16H-300F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006457 7

60206 RUBBER SILICONE RTV 3118 GID: DOXXXX
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.92	.32	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

60222 RUBBER SILICONE RTV 3120 GID: DOCKXX
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

05163 RUBBER SILICONE RTV 3140 GID: DOCKXX
MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.020	0.003		02.90	SMALL
X	1	025.9	014.3	0.010	0.003		01.40	MOD
X	1	030.0	009.0	0.012	0.003		01.00	MOD
A	1	030.0	010.4	0.019	0.003		01.40	SMALL
I	1	033.0	014.3	0.020	0.003	00.37	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.16	.06	.00	24H-302F- 168H-70F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	B	00019.72	168H-70F-

80986 RUBBER SILICONE RTV 3140 TOX RATE STUDY
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	V	00022.56	24H-70F- 24H-150F-

81841 RUBBER SILICONE RTV 3140 UNCURED
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	X	00021.35	

05646 RUBBER SILICONE RTV 3140/1204 GID: DOCKXX
MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.008	0.003	00.12	02.10	SMALL
A	1	030.0	010.0	0.002	0.003		02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.43	.09	.00	168H-70F- 46H-180F-0psiaVACUUM

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

05392 RUBBER SILICONE RTV 3144 GID: AKCKXX
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.75	.66	.00	720H-70F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	B	00024.41	168H-70F- 24H-150F-

05247 RUBBER SILICONE RTV 3145 GID: AKCKHD
MANF: DOW CORNING

SPEC: MB0120-097 MIL-A-46146T1

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006458 9

05247 RUBBER SILICONE RTV 3145 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.014			04.30	NONE
A	1	023.8	014.5	0.008	0.003		01.20	NONE
A	2	023.8	014.5	0.004	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.004	0.003		00.40	NONE
A	1	025.9	014.3	0.031	0.003		02.10	SMALL
A	1	030.0	009.0	0.023	0.003		01.30	NONE
A	1	033.0	014.3	0.026	0.003		02.20	SMALL

FSC

RT	FLUID NAME
A	HYZE
A	MMH
C	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.11	.01	.00	24H-70F- 24H-450F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00012.25	168H-70F- 24H-150F-

64456 RUBBER SILICONE RTV 3145/DC1200 GID: DPXXXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.040	0.005		01.80	NONE

FSC

No test data

OXYGEN COMP

No test data

05670 RUBBER SILICONE RTV 325 GID: DOCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.473			00.20	NONE

FSC

No test data

OXYGEN COMP

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.46	.36	.00	.05H-300F-

ODOR

No test data

TOXICITY

RT	WEIGHT	CURE

60388 RUBBER SILICONE RTV 345 GID: DOCKXX

MANF: DOW CORNING

SPEC: USBI99600-0010

....NO TEST DATA AVAILABLE....

05842 RUBBER SILICONE RTV 4515 GID: DODPXX

MANF: DOW CORNING

SPEC: MIL-R-5847C13

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.020		00.02	12.00	T SMALL
C	1	023.8	014.5	0.020		00.32	12.00	T NONE

FSC

No test data

OXYGEN COMP

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00037.01	

64105 RUBBER SILICONE RTV 501-7 GID: DOCKXX

MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00004.83	

80072 RUBBER SILICONE RTV 510

MANF: MCGHAN NUSIL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.064		00.10	12.00	T SMALL

FSC

No test data

OXYGEN COMP

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.35	.01		288H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	22.306	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006459 0

06262 RUBBER SILICONE RTV 511/577 GID: DOCKXX
MANF: SPEC: MB0130-119T1&3

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.65	.35	.00	72H-70F- 72H-51F-0psiaVACUUM

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

00551 RUBBER SILICONE RTV 511/SS4155 GID: DPCKXX
MANF: GENERAL ELECTRIC SPEC: MB0130-119T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.058	0.003		00.90	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.81	.25	.00	72H-70F- 90H-212F-0psiaVACUUM

ODOR / TOXICITY

RT	RT WEIGHT	CURE
B	00032.68	168H-70F- 24H-150F-

01039 RUBBER SILICONE RTV 560 GID: DOCKXX
MANF: GENERAL ELECTRIC SPEC: AMS 3195 MB0130-119T2
VB PER MA0105-064

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	030.0	014.3	0.031			06.30	SMALL
A	1	030.0	010.0	0.095			04.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	5.0E-7	.12	.03		24H-490F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00020.24	48H-70F- 24H-150F-

01036 RUBBER SILICONE RTV 560 COMPOS GID: DOCKXX
MANF: VB PER MA0105-064 SPEC: AMS 3195

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.30	.12	.08	16H-408F- 16H-400F-16H-400F/SEE MFG

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

64114 RUBBER SILICONE RTV 560 EPOXY/GLASS GID: EXXXXX
MANF: ROCKWELL SPEC: MB0130-105T8FR MB0130-119
ZZ-R-765

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	3.400			00.10	NONE
C	1	025.9	014.3	3.400		00.01	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.09	.03	.00	24H-257F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

80977 RUBBER SILICONE RTV 560 TOX RATE STUDY
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
X	00020.53	24H-70F- 24H-150F-

05156 RUBBER SILICONE RTV 560/577 GID: DPCKXX
MANF: GENERAL ELECTRIC SPEC: MB0130-119T2+3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.022	0.005		01.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006460 7

05156 RUBBER SILICONE RTV 560/577 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.060		00.30	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.57	.08	.00	720H-70F- 103H-167F-0psiaVACUUM

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00022.61	168H-70F-

63501 RUBBER SILICONE RTV 560/9811 GID: DRDSXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.090		00.07	01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.82	.46	.00	36H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00022.20	24H-70F-

06350 RUBBER SILICONE RTV 560/FILLED INCR3 GID: DOCKXX

.:..NO TEST DATA AVAILABLE....

03484 RUBBER SILICONE RTV 566 GID: DPCKXX

MANF: GENERAL ELECTRIC SPEC: MB0130-085 STM 0051-01
STM 0706-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.095			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-5	.12	.00	.10	2H-140F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00029.47	168H-70F- 24H-150F-

05410 RUBBER SILICONE RTV 567 GID: DOCKXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.52	.03	.00	120H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

62160 RUBBER SILICONE RTV 577 GID: BACKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.124			03.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	14.7	65	-314	0.118	00	20
C	MECH	50	30	-150	0.109	00	20
B	MECH	50	72	70	0.124	00	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.99	.57	.00	48H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

80987 RUBBER SILICONE RTV 577 TOX RATE STUDY

MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00020.35	

05306 RUBBER SILICONE RTV 577/9811 GID: DRDRXX

MANF: GENERAL ELECTRIC SPEC: GD541 & FB117

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.057	0.003		00.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		70	0.052	2	08

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006461 9

05306 RUBBER SILICONE RTV 577/9811 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	1500	72	70	0.060	2	27

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.4E-6	2.66	.57		24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00021.42	24H-70F- 24H-150F-

00987 RUBBER SILICONE RTV 577/T12 GID: DODPXX

MANF: GENERAL ELECTRIC SPEC: MB0130-119T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	009.0	0.074		00.28	11.80	T NONE
A	1	030.0	010.4	0.053	0.003		02.50	SMALL
I	1	030.0	010.4	0.103		00.08	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	3.04	1.27	.01	24H-70F- 20H-165F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.50	168H-70F- 24H-150F-

05889 RUBBER SILICONE RTV 60 GID: ABCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.067			01.70	NONE
C	1	023.8	014.5	0.067		00.06	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.69	.54	.00	24H-300F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00167.81	168H-70F- 24H-150F-

05510 RUBBER SILICONE RTV 602 CLEAR GID: DOCKXX

MANF: GENERAL ELECTRIC SPEC: MB0130-068

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.130			00.40	NONE
C	1	023.8	014.5	0.130		00.04	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.89	.01	.00	24H-149F- 168H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00019.92	96H-70F-IN OPEN MOLD

06364 RUBBER SILICONE RTV 602/GL-FR GID: DOCKXX

....NO TEST DATA AVAILABLE....

05397 RUBBER SILICONE RTV 615 GID: AZCKHD

MANF: GENERAL ELECTRIC SPEC: ST68S598-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.049	0.003		01.10	SMALL
A	1	025.9	014.3	0.004	0.003		01.20	NONE
I	1	030.0	010.0	0.052		00.17	12.00	T SMALL
A	1	033.0	014.3	0.004	0.003		01.70	NONE
X	1	100.0	020.2	0.004	0.003	02.07	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	.89	.36		1H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00019.88	1H-150F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006462 0

05397 RUBBER SILICONE RTV 615 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					1H-220F-

ODOR

RT	RT	WEIGHT	CURE
			1H-220F-

TOXICITY

20436 RUBBER SILICONE RTV 616 GID: DOCKXX

MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.41	.66	.00	1H-212F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05038 RUBBER SILICONE RTV 630 GID: BADSXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.105	0.003	00.04	00.10	NONE
C	1	030.0	010.0	0.105	0.003	00.03	11.90	T SMALL

FSC

RT	FLUID NAME
A	AMMONIA

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.11	.02	.00	24H-250F-0psiaVACUUM

ODOR

RT	RT	WEIGHT	CURE
A	B	00020.33	1H-200F-
			.5H-300F-

TOXICITY

06613 RUBBER SILICONE RTV 630/50% OIL GID: DPCKXX

MANF: GENERAL ELECTRIC SPEC: SF-96-5

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.025		00.10	12.00	T MOD
X	1	025.9	014.3	0.025		00.20	11.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00019.39	

TOXICITY

05701 RUBBER SILICONE RTV 632 GID: DPCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.016	0.003		01.20	NONE
C	2	030.0	010.0	0.130			00.10	NONE
C	1	030.0	010.0	0.130		00.10	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.25	.74	.00	48H-70F-
					24H-300F-

ODOR

RT	RT	WEIGHT	CURE
	V	00019.99	1H-212F-

TOXICITY

05883 RUBBER SILICONE RTV 634 GID: DOCKXX

MANF: GENERAL ELECTRIC SPEC: MIL-S-23586

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.5	0.235			00.20	NONE
A	1	023.8	014.5	0.235			00.20	NONE
B	1	025.9	014.3	0.230			06.10	NONE
A	1	025.9	014.3	0.012	0.003		01.00	NONE
A	1	030.0	014.3	0.233	0.003		06.20	SMALL
A	1	030.0	009.0	0.018			00.60	NONE
A	1	033.0	014.3	0.010			02.40	NONE
X	1	033.2	015.5	0.225		00.02	11.90	T MOD
I	1	035.0	014.3	0.230		00.03	11.90	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006463 2

05883 RUBBER SILICONE RTV 634 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	035.0	009.0	0.016			01.10	NONE
X	1	040.0	014.3	0.225	0.003	00.03	11.90	T MOD
X	1	050.0	014.3	0.225		00.06	11.90	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00020.12	168H-70F- 24H-150F-

05419 RUBBER SILICONE RTV 6508 GID: CHCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.120		00.05	11.80	T MOD
X	1	100.0	016.5	0.120		00.39	11.80	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.21	.07	.00	.08H-241F- 1.5H-421F- 24H-250F-0psiaVACUUM

FSC

RT	FLUID NAME
A	AMMONIA

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05489 RUBBER SILICONE RTV 651 GID: DOCKXX

MANF: DOW CORNING

SPEC: AMS 3335

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.068			00.50	NONE
C	1	023.8	014.5	0.068		00.06	12.00	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	.38	.17		

FSC

RT	FLUID NAME
A	AMMONIA

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	72	-297	0.065	1	20

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.82	

60278 RUBBER SILICONE RTV 652 GID: DOCKXX

MANF: GENERAL ELECTRIC

....NO TEST DATA AVAILABLE....

60290 RUBBER SILICONE RTV 655 GID: DOCKXX

MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.55	.96	.00	168H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

06520 RUBBER SILICONE RTV 664 GID: DOCKXX

....NO TEST DATA AVAILABLE....

05217 RUBBER SILICONE RTV 69-210 GID: CHCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.008	0.003		01.30	SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.02	.01	.00	16H-482F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00018.16	24H-70F-

62371 RUBBER SILICONE RTV 700 GID: DOCKXX

MANF: GENERAL ELECTRIC

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006464 4

62371 RUBBER SILICONE RTV 700 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.51	.32	.00	16H-399F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	V	00020.29	24H-70F-

60308 RUBBER SILICONE RTV 730 GID: DDXXXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010	0.003		01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.3E-6	5.41	.20	.02	168H-70F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
X	B	00020.14	168H-70F-

06556 RUBBER SILICONE RTV 738 GID: DODPXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.111			00.20	NONE
C	1	025.9	014.3	0.111		00.88	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	X	00019.99	49H-70F-

64451 RUBBER SILICONE RTV 7500-511/FIBERGLASS GID: DOGDX

MANF: G & D INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.067			02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64452 RUBBER SILICONE RTV 77 GID: DOCKXX

MANF: SPEC: RB0120-005 T8

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		03.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	1.69	1.02	.00	8H-70F- 24H-302F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

06192 RUBBER SILICONE RTV 8111/C9889 GID: DPCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010	0.003		01.80	NONE
A	1	033.0	014.3	0.010	0.003		02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.36	.41	.00	16H-70F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	B	00019.88	24H-70F- 24H-150F-

06495 RUBBER SILICONE RTV 8112 C9858 GID: DOCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.040			06.10	SMALL
C	1	025.9	014.3	0.040		00.17	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006465 6

06495 RUBBER SILICONE RTV 8112 C9858 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.33	.36	.00	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	B	00020.42	24H-70F-

05415 RUBBER SILICONE RTV 8112/C9891 GID: DPCKXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.36	.41	.00	16H-70F-

ODOR / TOXICITY

No test data

60310 RUBBER SILICONE RTV 855 GID: DPCKXX

MANF: PROD RESEARCH & CHEM SPEC: USB-MS-2005

....NO TEST DATA AVAILABLE....

06108 RUBBER SILICONE RTV 881 GID: DOCKXX

....NO TEST DATA AVAILABLE....

05618 RUBBER SILICONE RTV 90 GID: DOCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.116			00.10	NONE
C	1	023.8	014.5	0.116		00.06	12.00	T NONE

FSC

RT	FLUID NAME
A	AMMONIA

OXYGEN COMP

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.62	.49	.00	24H-302F-

ODOR / TOXICITY

No test data

05777 RUBBER SILICONE RTV 955 GID: DOCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.103			04.90	MOD
X	1	030.0	010.0	0.103		00.09	08.70	MOD

FSC

No test data

OXYGEN COMP

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.76	.26	.00	.25H-160F- 6H-350F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	A	10.182	

60384 RUBBER SILICONE RTV DC3-6077 GID: DOXXXX

MANF: DOW CORNING
GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.041			03.80	NONE

FSC

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.025	01	01
C	MECH	14.7	30	-314	0.075	00	20
C	MECH	14.7	35	-314	0.125	00	20
C	MECH	50	20	-150	0.025	00	20
B	MECH	50	72	-150	0.077	00	20
C	MECH	50	45	-150	0.077	00	20
B	MECH	50	72	70	0.025	00	20
B	MECH	50	72	70	0.077	00	20
B	MECH	50	72	70	0.125	00	20

05227 RUBBER SILICONE RTV DC6-1104 GID: AKCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.038	0.003		02.30	SMALL

FSC

No test data

OXYGEN COMP

No test data

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006466 8

05227 RUBBER SILICONE RTV DC6-1104 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.100		00.08	01.90	SMALL

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.15	.02	.00	24H-46F- 24H-151F- 168H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00048.58	24H-70F- 24H-150F-

05195 RUBBER SILICONE RTV DC96-080 GID: ABCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.007		00.00	00.00	NONE
A	1	023.8	014.5	0.007			01.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.48	.11	.00	168H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00024.18	24H-150F-

61117 RUBBER SILICONE RTV R1500 GID: DOCKXX

MANF: MCGHAN NUSIL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.7E-6	.43	.06	.02	168H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

61118 RUBBER SILICONE RTV R2500 GID: DOCKXX

MANF: MCGHAN NUSIL SPEC: RD-004-056A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.5E-6	.27	.05	.02	.5H-212F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

60730 RUBBER SILICONE RTV R2501 GID: ABCKXX

MANF: MCGHAN NUSIL SPEC: RD-004-056A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.2E-6	.36	.07	.01	24H-70F- 4H-150F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

61119 RUBBER SILICONE RTV R2510 GID: DOCKXX

MANF: MCGHAN NUSIL

THER AL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.1E-6	2.35	1.36	.03	24H-70F- 168H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

61120 RUBBER SILICONE RTV R2520 GID: DOCKXX

MANF: MCGHAN NUSIL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.55	.06		48H-70F- 2H-150F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

61112 RUBBER SILICONE RTV R2566 GID: DOCKXX

MANF: MCGHAN NUSIL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.94	.03		48H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006467 T

61112 RUBBER SILICONE RTV R2566 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					2H-150F-

ODOR

RT	RT WEIGHT	CURE

TOXICITY

61108 RUBBER SILICONE RTV R2567 GID: DOCKXX

MANF: MCGHAN NUSIL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.62	.05	.00	

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

20420 RUBBER SILICONE RTV SWS930 GID: DOCKXX

MANF: SWS SILICONES

....NO TEST DATA AVAILABLE....

06237 RUBBER SILICONE RTV SWS951 GID: DOCKXX

MANF: SWS SILICONES

SPEC: MB0120-108

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.010	0.003		00.90	SMALL

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.06	.05	.00	4H-257F-0psiaVACUUM

ODOR

RT	RT WEIGHT	CURE
A	B 00019.98	168H-70F-

TOXICITY

62379 RUBBER SILICONE RTV SWSV81 GID: DOHDCK

MANF: SWS SILICONES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.8E-6	1.01	.25	.04	4H-150F-
					24H-70F-

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

06182 RUBBER SILICONE RUBBERCRAFT 59 GID: DOCKXX

MANF: RUBBERCRAFT

....NO TEST DATA AVAILABLE....

61418 RUBBER SILICONE S317 GID: CHCKXX

MANF: PARKER SEAL

SPEC: ZZ-R-765

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.053			02.20	NONE
C	1	023.8	014.5	0.053		00.12	11.90	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.6E-6	1.08	.31		

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

06090 RUBBER SILICONE S383-70 GID: DOCKXX

MANF: PARKER SEAL

SPEC: AMS 3337

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.047			04.00	MOD

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1500	40	70		1	02
I	PNEU	1500		70	0.072	1	05

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	.30	.02		

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

06373 RUBBER SILICONE S455-70 GID: DOCKXX

MANF: PARKER SEAL

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006468 1

06373 RUBBER SILICONE S455-70 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.53	.01	.00	1H-248F- 2H-266F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	25.05	

05570 RUBBER SILICONE S469-40 GID: DOCKXX

MANF: PARKER SEAL

SPEC: AMS 3301

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	023.8	014.5	0.053		00.10	11.70	T SMALL
C	2	023.8	014.5	0.020			08.40	NONE
C	1	023.8	014.5	0.020		00.31	12.00	T NONE
C	2	023.8	014.5	0.010		00.04	12.00	T NONE
C	1	023.8	014.5	0.010		00.66	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00010.17	

05740 RUBBER SILICONE S571 GID: DOCKXX

MANF: ALL SEALS INC

SPEC: AMS 3301

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.077		00.10	11.70	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.5E-6	2.01	.76		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.71	

60521 RUBBER SILICONE S59 GID: CHCKXX

MANF: ROBERTSHAW

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	4000		70	0.074	02	07
Z	MECH	4000	72	70	0.074	02	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00020.62	

05343 RUBBER SILICONE S604-70 GID: DOCKXX

MANF: PARKER SEAL

SPEC: AMS 3304

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	PNEU	100		70	0.075	0	02
Z	MECH	100	72	70	0.075	01	06

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.7E-7	1.46	.38		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00020.04	

05447 RUBBER SILICONE S614-80 GID: DOCKXX

MANF: CARLETON CONTROLS
PARKER SEAL

SPEC: ZZ-R-765 CL 2A & 2B GR 80

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.129			08.30	NONE
B	1	025.9	014.3	0.130			07.30	NONE
I	1	100.0	016.5	0.130			12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		200	0.031	4	05
B	PNEU	1000		70	0.069	0	22
Z	MECH	1000	72	70	0.075	2	06
X	MECH	1050	15	70	0.070	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006469 3

05447 RUBBER SILICONE S614-80 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1050	35	70	0.070	2	13
X	PNEU	1050		70	0.074	2	79
X	PNEU	1500		200	0.031	2	02
X	PNEU	2000		200	0.031	3	06
B	PNEU	2000		70	0.069	0	20
X	PNEU	2500		200	0.031	2	02
X	PNEU	2500		70	0.069	2	25
X	PNEU	3000		70	0.069	3	13
X	MECH	3300	15	200	0.035	0	20
X	PNEU	3500		70		3	16
X	MECH	3670	10	70	0.072	0	20
Z	MECH	3670	35	70	0.072	2	02
B	PNEU	500		200	0.031	0	40
X	PNEU	5000		70	0.069	3	08
X	PNEU	6000		70	0.069	1	08
X	PNEU	7000		70	0.069	1	02
I	PNEU	750		70	0.077	0	10
X	MECH	7500	10	70	0.078	0	12

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.0E-7	1.81	.47		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00010.19	

60782 RUBBER SILICONE S64 GID: CHCKXX

MANF: ROBERTSHAW

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	4000		70	0.074	02	06
X	PNEU	4000		70	0.074	2	06
Z	MECH	4000	72	77	0.074	02	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.28	

06111 RUBBER SILICONE S6535 GID: DOCKXX

MANF: DOW CORNING

....NO TEST DATA AVAILABLE....

60783 RUBBER SILICONE S66 GID: CHCKXX

MANF: ROBERTSHAW

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	4000		70	0.074	2	03
Z	MECH	4000	72	75	0.074	2	04

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.62	

20650 RUBBER SILICONE S899-50 GID: DOCKXX

MANF: KIRKHILL RUBBER

SPEC: ZZ-R-765BC3BG50

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.067			02.50	SMALL
B	1	033.0	014.3	0.068			07.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	.68	.22		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.63	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006470 T

05493 RUBBER SILICONE SE4404 GID: DOCKXX

MANF: GENERAL ELECTRIC SPEC: MIL-R-3065

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.025		00.30	11.70	T NONE
I	1	025.9	014.3	0.080		0.026	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70		0	20
X	PNEU	1500		70		1	20
X	PNEU	2000		70		1	17
X	PNEU	3000		70		1	01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.10	.01	.00	24H-480F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00044.97	

85386 RUBBER SILICONE SE4404U WITH SIO2 FILLER GID: DOCKXX

MANF: HADBAR
PARKER SEAL
UVEXS CORP
SPEC: ZZ-R-765 CL 2B GR 70

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.13	.03	.05	

ODOR

No test data

TOXICITY

RT	WEIGHT	CURE

85436 RUBBER SILICONE SE4404U WITH SIO2 FILLER WITH CHOBOND 320 ADHESIVE GID: DOXXXX

MANF: HADBAR/CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.093		00.01	0.25	T NONE

FSC

No test data

OXYGEN COMP

No test data

20367 RUBBER SILICONE SE4552 GID: DOCKXX

....NO TEST DATA AVAILABLE....

63028 RUBBER SILICONE SE5206V GID: DODPXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.5	0.069			05.00	NONE

FSC

No test data

OXYGEN COMP

No test data

05445 RUBBER SILICONE SE5211 GID: DOCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.065			05.50	NONE
B	1	025.9	014.3	0.031		00.03	09.00	NONE
X	1	025.9	014.3	0.107		00.04	05.70	T MOD

FSC

No test data

OXYGEN COMP

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.08	.02	.00	4H-480F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.02	

05423 RUBBER SILICONE SE5403 GID: CHDPXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.115		00.04	11.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70	0.115	0	20
X	MECH	1000	72	70	0.115	02	04
X	PNEU	250		70	0.010	02	20
X	PNEU	250		70	0.010	2	20
X	MECH	250	72	70	0.010	02	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.10	.02	.00	2H-399F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.80	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006471 1

20366 RUBBER SILICONE SE550 GID: DOCKXX
MANF: ROBERTSHAW

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	250		70	0.035	0	20
C	MECH	250	72	70	0.035	2	02

62030 RUBBER SILICONE SE5549 GID: DOCKXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.095			00.10	NONE
C	1	025.9	014.3	0.095		00.03	05.80	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.69	.31		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.07	

TOXICITY

62031 RUBBER SILICONE SE5559 GID: DOCKXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.091			04.30	NONE
C	1	033.0	014.3	0.091			05.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-7	.82	.25		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.44	

TOXICITY

05424 RUBBER SILICONE SE5601 GID: DOCKXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.051			05.20	NONE
I	1	025.9	014.3	0.105		00.06	05.70	T NONE
I	1	100.0	016.5	0.053		00.43	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70	0.050	0	20
C	MECH	1000	30	70	0.050	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.2E-5	.26	.06		

ODOR

RT	RT	WEIGHT	CURE
A	A	00099.49	

TOXICITY

20648 RUBBER SILICONE SE565 GID: DOCKXX
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.25	.12	.00	2H-351F- 120H-351F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05958 RUBBER SILICONE SE7600 GID: DOCKXX
MANF: GENERAL ELECTRIC
....NO TEST DATA AVAILABLE....

84021 RUBBER SILICONE SI400
MANF: BOYD INDUSTRY RUBBER
....NO TEST DATA AVAILABLE....

84022 RUBBER SILICONE SI500
MANF: BOYD INDUSTRY RUBBER
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006472 3

01838 RUBBER SILICONE SI503 GID: DOCKXX

....NO TEST DATA AVAILABLE....

84718 RUBBER SILICONE SI600

MANF: BOYD INDUSTRY RUBBER

....NO TEST DATA AVAILABLE....

20576 RUBBER SILICONE SI644-01 GID: DOCKXX

....NO TEST DATA AVAILABLE....

84720 RUBBER SILICONE SI700

MANF: BOYD INDUSTRY RUBBER

....NO TEST DATA AVAILABLE....

63196 RUBBER SILICONE SILIGAN J500

MANF: SWS SILICONES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.037		00.40	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05735 RUBBER SILICONE SM3500-41 GID: DOCKXX

MANF: DOW CORNING
ITT CANNON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.069			02.50	NONE
C	1	030.0	010.0	0.069		00.10	11.50	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.39	.13	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	10.090	

20700 RUBBER SILICONE SM3500-53

....NO TEST DATA AVAILABLE....

06158 RUBBER SILICONE SM3500-55 GID: DOCKXX

....NO TEST DATA AVAILABLE....

20701 RUBBER SILICONE SM3500-66

....NO TEST DATA AVAILABLE....

06385 RUBBER SILICONE SMC1050 GID: DQDPXX

SPEC: MB0130-169

MANF: D AIRCRAFT PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.035			00.50	NONE
C	1	020.9	014.7	0.035		00.12	12.00	T NONE

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.6E-6	1.83	.50	.08	1H-345F-65psiaUNDER A FULL VACUUM.

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

05466 RUBBER SILICONE SONFARREL 1151 GID: CHCKXX

SPEC: AMS 3302

MANF: SONFARREL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.064			02.50	NONE
X	1	023.8	014.5	0.064			12.00	T MOD

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00116.70	

62002 RUBBER SILICONE SR200 GID: EGCKXX
MANF: L FRANK MARKEL & SON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.034			12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.4E-6	1.00	.46		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00010.92	

63029 RUBBER SILICONE SR50 GID: DOCKXX
MANF: TIGERS POLYMER CORP SPEC: JIS K638 C1503

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.091		00.50	01.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00261.20	

05793 RUBBER SILICONE SRB0607 GID: DOCKXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.008		00.36	11.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.7E-6	.43	.19		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00014.88	

20029 RUBBER SILICONE SWS7220 GID: DOCKXX
MANF: SIERRA ENGINEERING
STAUFFER CHEMICAL
SWS SILICONES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3				07.50	SMALL
B	1	025.9	014.3				06.50	NONE
X	1	025.9	014.3	0.085			08.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63030 RUBBER SILICONE SWS7220/7250 GID: DOCKXX
MANF: SWS SILICONES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.615			01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65363 RUBBER SILICONE SWS845 CAT KX GID: DODPXX
MANF: SWS SILICONES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00022.83	24H-70F- 48H-70F-

64453 RUBBER SILICONE T8296 GID: DOCKXX
MANF: ITT CANNON SPEC: SM3500-41

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.180			00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006474 7

05884 RUBBER SILICONE TA52 GID: DOCKXX
MANF: T A MFG CORP
....NO TEST DATA AVAILABLE....

20639 RUBBER SILICONE TA96 GID: DOXXXX
MANF: T A MFG CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.072			05.90	SMALL
A	1	030.0	009.0	0.072			03.50	SMALL
X	1	100.0	020.2	0.072		00.49	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.0E-6	.71	.32		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.43	

64098 RUBBER SILICONE TH1006 GID: DODPXX
MANF: STILLMAN RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.71	.51	.00	72H-400F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

06149 RUBBER SILICONE TH1217 GID: CHCKXX
MANF: SARGENT INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.125			12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	500		70	0.125	0	20
B	MECH	500	72	70	0.125	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	1.29	.43		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.00	

61508 RUBBER SILICONE TH1241 GID: DOCKXX
MANF: STILLMAN RUBBER
SPEC: AMS 3301

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.054		00.02	12.00	T NONE
C	1	023.8	014.5	0.054		00.21	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.9E-6	1.85	.81		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00048.47	

06150 RUBBER SILICONE TH1242/TH1165 GID: DOCKXX
MANF:
SPEC: AMS 3302
....NO TEST DATA AVAILABLE....

06148 RUBBER SILICONE TH1243/TH1166 GID: DOCKXX
MANF:
SPEC: AMS 3303
....NO TEST DATA AVAILABLE....

60060 RUBBER SILICONE THERMAL CONDUCTIVE GID: DOCKXX
MANF: BERGQUIST
SPEC: MIL-S-8660
....NO TEST DATA AVAILABLE....

62393 RUBBER SILICONE TSC11 GID: DODPXX
MANF: TELEDYNE BROWN ENG

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.9E-6	1.09	.43	.01	720H-70F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006475 9

62393 RUBBER SILICONE TSC11 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					4H-150F-0psiaVACUUM

ODOR

RT	RT WEIGHT	CURE

TOXICITY

61420 RUBBER SILICONE WITH WIRE MESH GID: CHDPXX

MANF: METEX

SPEC: AMS 3195

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.157		00.58	09.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	8.9E-6	2.68	1.21		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62846 RUBBER SILICONE/ALUMINUM/DC282 GID: DOCKFK

MANF: MARTIN MARIETTA

SPEC: ZZ-R-765

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.507		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20009 RUBBER SPONGE NEOPRENE GID: DODBXX

MANF: ARMSTRONG
WESTINGHOUSE

SPEC: MIL-R-6130T1GRA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.3	0.200			00.10	NONE
X	1	020.9	014.3	0.200		00.34	12.00	T MOD
X	2	020.9	014.7	0.185			00.10	NONE
X	1	020.9	014.7	0.185		019	12.00	T NONE
X	1	023.8	014.5	0.120		00.19	11.80	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00020.69	

TOXICITY

63208 RUBBER SPONGE VITON GID: DODFXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.100			02.50	SMALL
A	1	020.9	014.7	0.250			01.00	NONE
A	1	023.8	014.5	0.100			03.00	NONE
A	1	023.8	014.5	0.250			03.00	SMALL
A	1	025.9	014.3	0.100			03.00	SMALL
A	1	025.9	014.3	0.250			04.00	SMALL
A	1	030.0	009.0	0.100			03.00	SMALL
A	1	030.0	009.0	0.250			03.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61662 RUBBER SR2702-75 GID: DOXXXX

MANF: PARKER SEAL
SARGENT INDUSTRIES
STILLMAN RUBBER

SPEC: MIL-R-83248T1C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70	0.070	0	20
B	PNEU	1050		120	0.058	0	100
C	MECH	1050	45	120	0.061	02	09
C	MECH	1050	72	120	0.062	0	12
X	PNEU	1050		120	0.062	4	79

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006476 0

61662 RUBBER SR2702-75 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1250		120	0.061	12	31
C	MECH	1250	25	120	0.065	0	20
B	MECH	245.0	72	70	0.031	00	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	1.03	.68	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

62312 RUBBER STOCKWELL 2023 GID: DOXXXX
MANF: STOCKWELL RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.130		00.04	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00019.96	

62184 RUBBER SUCTION CUP GID: DDHDXX
MANF: STILSON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	1.000		00.23	06.00	T MOD
X	1	023.8	014.5	1.500		00.17	05.10	T MOD
C	2	025.9	014.3				00.20	NONE
C	1	025.9	014.3				00.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	A 00413.78	

85054 RUBBER SYLGARD 527
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85055 RUBBER SYLGARD 567
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

85056 RUBBER SYLGARD 577
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

20129 RUBBER SYNTHETIC 11-102-1 GID: DOCBXX
MANF: AGC INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.075			01.80	NONE
C	1	023.8	014.5	0.075		00.21	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-6	10.55	6.56		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.01	

05484 RUBBER SYNTHETIC MS35489 GID: DODJXX
MANF: MINOR RUBBER CO SPEC: MIL-G-3036
RUBBERCRAFT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7			00.09	01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006477 2

05484 RUBBER SYNTHETIC MS35489 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.015			08.60	MOD
X	1	023.8	014.5	0.015		01.14	12.00	T NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.9E-7	14.03	7.48		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00027.76	

83207 RUBBER TELCAR 101
MANF: APEX
....NO TEST DATA AVAILABLE....

83208 RUBBER TELCAR 102
MANF: APEX
....NO TEST DATA AVAILABLE....

83209 RUBBER TELCAR 150
MANF: APEX
....NO TEST DATA AVAILABLE....

83210 RUBBER TELCAR 301
MANF: APEX
....NO TEST DATA AVAILABLE....

83211 RUBBER TELCAR 302
MANF: APEX
....NO TEST DATA AVAILABLE....

83212 RUBBER TELCAR 310
MANF: APEX
....NO TEST DATA AVAILABLE....

83213 RUBBER TELCAR 312
MANF: APEX
....NO TEST DATA AVAILABLE....

83214 RUBBER TELCAR 332
MANF: APEX
....NO TEST DATA AVAILABLE....

83215 RUBBER TELCAR 340
MANF: APEX
....NO TEST DATA AVAILABLE....

83217 RUBBER TELCAR 340E
MANF: APEX
....NO TEST DATA AVAILABLE....

83216 RUBBER TELCAR 340S
MANF: APEX
....NO TEST DATA AVAILABLE....

83218 RUBBER TELCAR 355
MANF: APEX
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006478 4

05099 RUBBER TIRE TREAD 17149 GID: DOXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.26	.97	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60067 RUBBER TR3005 GID: DODHXX

MANF: KIRKHILL RUBBER SPEC: STW5-2643

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.400		00.12	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20466 RUBBER TROLEN GID: DOXXXX

....NO TEST DATA AVAILABLE....

81755 RUBBER URALANE 1440 A/B

MANF: FURANE

....NO TEST DATA AVAILABLE....

81756 RUBBER URALANE 1460 A/B

MANF: FURANE

....NO TEST DATA AVAILABLE....

81757 RUBBER URALANE 87645 A/B

MANF: FURANE

....NO TEST DATA AVAILABLE....

81758 RUBBER URALANE 87647 A/B

MANF: FURANE

....NO TEST DATA AVAILABLE....

82025 RUBBER URALITE 3121S

MANF: HEXCEL

....NO TEST DATA AVAILABLE....

82026 RUBBER URALITE 3130

MANF: HEXCEL

....NO TEST DATA AVAILABLE....

82027 RUBBER URALITE 3136

MANF: HEXCEL

....NO TEST DATA AVAILABLE....

82028 RUBBER URALITE 3138

MANF: HEXCEL

....NO TEST DATA AVAILABLE....

82029 RUBBER URALITE 3140

MANF: HEXCEL

....NO TEST DATA AVAILABLE....

82030 RUBBER URALITE 3142

MANF: HEXCEL

....NO TEST DATA AVAILABLE....

82031 RUBBER URALITE 3148

MANF: HEXCEL

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006479 6

82032 RUBBER URALITE 3150
MANF: HEXCEL
....NO TEST DATA AVAILABLE....

82033 RUBBER URALITE 3154
MANF: HEXCEL
....NO TEST DATA AVAILABLE....

80288 RUBBER URETHANE CYANAPRENE 3090 GID: CAXXXX
MANF: AMERICAN CYANAMID
GRUMMAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.075		0.07	03.00	LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	31.5	

63504 RUBBER URINE COLLECTION TUBE
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00007.31	

84669 RUBBER US0059
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84670 RUBBER US0066
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84671 RUBBER US0075
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84673 RUBBER US0081
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84674 RUBBER US0082
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84676 RUBBER US0083
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

84678 RUBBER US0084
MANF: HYSOL/DEXTER
....NO TEST DATA AVAILABLE....

20600 RUBBER VACUBASE GID: DOXXXX
....NO TEST DATA AVAILABLE....

84857 RUBBER VESTAMID E40-S3
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006480 2

84862 RUBBER VESTAMID E47-S3
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84859 RUBBER VESTAMID E50-C5-S2
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84864 RUBBER VESTAMID E55-S3
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84866 RUBBER VESTAMID E57-C5-S2
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84870 RUBBER VESTAMID E62-S3
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

84873 RUBBER VESTAMID E67-C5-S2
MANF: NUODEX INC
....NO TEST DATA AVAILABLE....

05284 RUBBER VISTANEX MML100 BUTYL GID: DOZZXX
MANF: EXXON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.298		00.06	12.10	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.12	.01		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00019.30	

63033 RUBBER VITON GID: DODEXX
MANF: DIXIE CLAY
FLUID POWER
NIPPON VALGUA IND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.029			02.50	NONE
A	1	024.5	014.3	0.112			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		77	0.060	00	20
X	PNEU	2000		77	0.060	02	08
B	PNEU	500		77	0.060	00	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.47	.05	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

84797 RUBBER VITON 1097
MANF: BRIGGS RUBBER PROD
....NO TEST DATA AVAILABLE....

60686 RUBBER VITON 133 ELASTOMER GID: DVDFAD
MANF: A D LITTLE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.038		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.05	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006481 4

20136 RUBBER VITON 1502 H41 GID: DODEXX
MANF: VERNAY LABORATORIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.063			00.60	NONE
A	1	033.0	014.3	0.063			03.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		250	0.061	0	20
I	MECH	1500	10	250	0.061	0	20
B	MECH	250	72	250	0.061	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	10.02	5.65	.00	

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.05	

TOXICITY

05906 RUBBER VITON 19357 GID: DODEXX
MANF: PRECISION RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1000	72	67	0.062	1	1
B	PNEU	1000		70	0.062	0	20
Z	MECH	1500	72	67	0.062	1	1
X	PNEU	1500		70	0.062	2	40
Z	MECH	2000	72	67	0.062	1	1
X	PNEU	2500		70	0.062	3	17
Z	MECH	3000	72	67	0.062	1	1
X	PNEU	3500		70	0.062	2	04
Z	MECH	500	72	67	0.062	2	9
C	MECH	5500	45	250	0.062	00	20

60924 RUBBER VITON 2702-75 GID: DODEXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	400	10	-297	0.5	01	20

65306 RUBBER VITON 3-912V GID: DOXXXX
MANF: PARKER HANNIFIN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	400	10	-297	0.115	0	20

65305 RUBBER VITON 3-916V GID: DOXXXX
MANF: PARKER HANNIFIN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	400	10	-297	0.113	1	20

61248 RUBBER VITON 744-75 GID: CHDEXX
MANF: PARKER SEAL

SPEC: MIL-R-83248

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1500	72	70	0.062	3	6
X	MECH	5500	10	70	0.062	0	20

65092 RUBBER VITON 75 GID: DOXXXX
MANF: PARKER HANNIFIN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	400	10	-297	0.050	1	01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.65	.08	.53	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

MSFC-HDBK-527 REV F 9999942 0006482 6

Information Handling Services, 2000

80200 RUBBER VITON 840627 (1320-75) GID: DOXXXX

MANF: DAINICHI NIHON DENSHI CO SPEC: MIL-R-25897TIG70

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.120			00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	21.485	

61029 RUBBER VITON 871 GID: DOXXXX

MANF: GROVE VALVE & REGULATOR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70	0.097	0	60
X	PNEU	1500		70	0.095	3	54
X	PNEU	2000		70	0.040	5	128
B	PNEU	2500		70		0	40
B	PNEU	2500		70		8	58
X	PNEU	2500		70	0.060	0	40
X	PNEU	2500		70	0.060	8	58
X	PNEU	3000		70	0.060	9	30
X	PNEU	3500		70	0.092	5	11
B	PNEU	4000		70	0.011	0	20
X	PNEU	4000		70	0.060	6	39
X	PNEU	4500		70	0.011	4	16
B	PNEU	5000		70	0.060	0	20
B	PNEU	5500		70	0.060	0	20
X	PNEU	6000		70	0.060	0	40
X	PNEU	6000		70	0.060	7	22
B	PNEU	6000		70	0.125	0	40
B	PNEU	6000		70	0.125	7	22

61942 RUBBER VITON 8846 GID: DOXXXX

MANF: PRECISION ASSOCIATES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	2000		70		0	20
X	PNEU	3000		70		1	07
X	PNEU	3500		70		1	04
X	PNEU	4000		70		1	01

61803 RUBBER VITON 8946 GID: DOXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70	0.090	0	20
X	PNEU	1500		70	0.090	1	20
X	PNEU	2000		70	0.090	1	02

05905 RUBBER VITON 9009-75 GID: DODEXX

MANF: PARCO PLASTIC & RUBBER CO SPEC: MIL-R-83248T1C1 MS83248/1-904

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	70	0.062	2	19
Z	MECH	1500	72	70	0.062	1	7
Z	MECH	2000	72	70	0.062	1	1
B	PNEU	2500		70	0.062	0	40

MSFC-HDBK-527 REV F 9999942 0006483 8

Information Handling Services, 2000

05905 RUBBER VITON 9009-75 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	3000		70	0.062	3	37
X	PNEU	3500		70	0.187	2	35
X	PNEU	4000		70	0.187	2	49
B	MECH	500	72	70	0.062	00	20
Z	MECH	5500	72	70	0.062	2	6
X	PNEU	5500		70	0.187	2	31
B	PNEU	6000		70	0.072	0	20
B	PNEU	6000		70	0.072	3	48
X	PNEU	6000		70	0.187	0	20
X	PNEU	6000		70	0.187	3	48

05904 RUBBER VITON 9009-90 GID: DODEXX
MANF: PLASTIC & RUBBER CO

SPEC: MIL-R-83248T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

MIL-R-83248T1C2

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	70	0.072	0	20
B	MECH	14.7	72	-297	0.072	5	20
B	MECH	1500	72	-297	0.072	0	20
B	PNEU	1500		70	0.062	0	20
B	MECH	1500	72	70	0.062	2	11.
B	MECH	1500	72	70	0.072	2	14
X	PNEU	2000		70	0.062	2	22
X	PNEU	3000		70	0.062	2	10
X	PNEU	4000		70	0.062	2	15
X	PNEU	5000		70	0.062	2	15
B	MECH	5500	72	70	0.062	2	12
C	MECH	5500	45	70	0.062	0	20
B	PNEU	6000		70	0.070	0	20
X	MECH	6000	15	70	0.120	0	20

62873 RUBBER VITON A GID: DODEXX
MANF: AMETEK
APPLIED RUBBER
B H HADLEY

SPEC: MIL-R-83248

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.031	4	30
B	MECH	14.7	72	-297	0.062	22	220

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.12	.61	.00	

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

62564 RUBBER VITON A 017-ESQ GID: DOXXXX
MANF: C & C PACKINGS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	PNEU	3000		70		0	03
B	PNEU	4000		70		0	20
X	PNEU	4500		70		1	15
X	PNEU	5000		70		1	09

62562 RUBBER VITON A 3-920 GID: DOXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	PNEU	3000		70	0.116	00	03

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006484 T

62562 RUBBER VITON A 3-920 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	4000		70	0.116	0	20
X	PNEU	4500		70	0.116	1	02
X	PNEU	5000		70	0.116	01	01

61079 RUBBER VITON A V23 GID: DODFDF
MANF: SEAL DYNAMICS
SPEC: MIL-R-83248

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	PNEU	2000		70	0.070	0	16
B	PNEU	4000		70	0.070	0	22
I	PNEU	4500		70	0.070	01	03
I	PNEU	4500		70	0.070	1	03
X	PNEU	5000		70	0.070	1	06
X	PNEU	5500		70	0.070	01	24
X	PNEU	5500		70	0.070	1	24
X	PNEU	6000		70	0.070	02	27
X	PNEU	6000		70	0.070	2	27
X	MECH	6000	15	70	0.070	01	08
B	PNEU	6000		70	0.103	0	20
C	MECH	6000	20	70	0.103	01	01

61075 RUBBER VITON A V709-90 GID: DODEXX
MANF: C E CONOVER
PARKER SEAL
SPEC: MIL-R-83248

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70	0.070	0	20
X	PNEU	2000		70	0.070	1	02
B	PNEU	3000		70	0.083	0	45
B	PNEU	3500		70	0.070	0	21
X	PNEU	4000		70	0.070	1	21
X	PNEU	5000		70	0.070	1	06
X	PNEU	5500		70	0.070	0	04
B	PNEU	6000		70	0.070	0	60
X	MECH	6000	10	70	0.070	0	18

61283 RUBBER VITON A V745-75 GID: DOCHXX
MANF: PARKER SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	2000		70	0.100	0	20
X	PNEU	2500		70	0.100	3	30
B	PNEU	4000		70	0.068	0	20
B	PNEU	4000		70	0.100	0	20
X	PNEU	4000		70	0.100	1	10
X	PNEU	4500		70	0.068	3	21
X	PNEU	5000		70	0.068	3	08
B	PNEU	5000		70	0.118	0	20
X	PNEU	5500		70	0.068	2	07
X	PNEU	6000		70	0.068	2	30

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.35	.02	.00	

ODOR

TOXICITY

RT	RT WEIGHT	CURE
No test data		

MSFC-HDBK-527 REV F 9999942 0006485 1

61331 RUBBER VITON A V86-678 GID: DODEXX

MANF: HIAWATHA RUBBER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70	0.059	0	20
X	PNEU	1500		70	0.059	3	07
X	PNEU	3000		70	0.059	2	06
X	PNEU	4000		70	0.059	2	11
X	PNEU	5500		70	0.059	2	03
X	PNEU	6000		70	0.059	1	01

63034 RUBBER VITON B50 GID: DVDFXX

MANF: APPLIED RUBBER
MCDONNELL DOUGLAS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.030			05.50	SMALL
A	1	025.9	014.3	0.030			06.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	5500	72	70	0.070	01	160

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00031.41	

63036 RUBBER VITON B50/DZ700610 GID: DODEXX

MANF: GOODYEAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.085			04.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63035 RUBBER VITON B50/DZ70D610 GID: DODEXX

MANF: GOODYEAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.065			03.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63040 RUBBER VITON B50/DZ70D613 GID: DODEXX

MANF: GOODYEAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.065			03.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64161 RUBBER VITON CHECK VALVE GID: DOXXXX

....NO TEST DATA AVAILABLE....

62147 RUBBER VITON CPD 68514A GID: DOXXXX

MANF: R F CARLSON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	2500		70	0.043	0	20
X	PNEU	3000		70	0.043	2	40
B	PNEU	4000		70	0.043	0	20
X	PNEU	4500		70	0.043	1	20

61891 RUBBER VITON CPD 8760 GID: DODFXX

MANF: ADVANCE RUBBER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	3000		70	0.085	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006486 3

61891 RUBBER VITON CPD 8760 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	3500		70	0.085	1	02
X	PNEU	4000		70	0.085	1	01

20637 RUBBER VITON E43060 GID: DOHDXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.053			03.10	NONE
C	1	033.0	014.3	0.053		00.09	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.16	.00		

ODOR

RT	RT	WEIGHT	CURE
A	A	00019.99	

TOXICITY

84230 RUBBER VITON E46315

MANF: DUPONT

....NO TEST DATA AVAILABLE....

63037 RUBBER VITON E60C GID: DODEXX

MANF: APPLIED RUBBER
DUPONT
KAIKUHL RUBBER

SPEC: MIL-R-83248T1C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.245		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	5500	72	70	0.070	00	120

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.20	.00	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

63038 RUBBER VITON E60C/HT426 NOMEX GID: DODEXX

MANF: DUPONT
STERN & STERN

SPEC: MIL-R-83248T2C1 STM0699-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.036			01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05005 RUBBER VITON FLUID RESISTANT GID: DVDFXX

MANF: ADTECH
AGC INC
AMETEK
ANCHOR PACKING CO
AVSCOA INC
C & C PACKINGS
CIRCLE SEAL
CONQUEST SEAL CORP
FLODYNE CONTROLS
JONAL LABORATORIES
KAIKUHL RUBBER
MOOG INDUSTRY
NUPRO COMPANY
PARCO
PARKER HANNIFIN
PARKER SEAL
PORTER SEAL
QSL

SPEC: AMS 7276
AS180-008
AS180-010
AS180-012
AS180-014
AS180-017
AS180-018
AS180-022
AS180-116
AS180-222
AS180-228
AS180-230
MC250-0002
ME251-0011
MIL-R-25897
MIL-R-83248
MIL-R-83248T1C1
MIL-R-83248T1C2
MIL-R-83248T2C1
MIL-R-83248T2C2
MIL-R-83286
MIL-R-832T1C1
RB0130-093 T1C1
TF70-R3A-01A

Information Handling Services, 2000

05005 RUBBER VITON FLUID RESISTANT (cont)

MANF: SARGENT INDUSTRIES
SOUTHWEST SEAL
STILLMAN RUBBER
TENNESSE VALVE
TENNESSEE VALLEY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.040			01.30	NONE
A	1	020.9	014.7	0.034			00.30	NONE
A	1	023.8	014.5	0.041			00.70	NONE
A	1	023.8	014.5	0.041			00.70	SMALL
A	1	025.9	014.3	0.051			01.60	SMALL
A	1	025.9	014.3	0.093			00.10	NONE
X	1	025.9	014.3	0.020		00.20	11.90	T MOD
A	1	025.9	014.3	0.034			04.20	SMALL
C	2	025.9	014.3	0.039			00.10	NONE
C	1	025.9	014.3	0.039		00.09	12.00	T SMALL
X	1	030.0	014.3	0.051		00.05	11.30	T MOD
A	1	030.0	009.0	0.090			00.10	NONE
A	1	030.0	009.0	0.100			00.30	NONE
X	2	030.0	010.0	0.014			00.10	NONE
X	1	030.0	010.0	0.014		00.09	10.40	LARGE
X	2	033.0	014.3	0.093			00.10	NONE
X	1	033.0	014.3	0.093		00.04	12.00	T MOD
C	2	033.0	014.3	0.060			00.40	SMALL
C	1	033.0	014.3	0.060		00.09	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1000	72	70		2	4
X	PNEU	1000		70	0.080	1	54
B	MECH	1050	72	70	0.069	0	20
Z	MECH	1050	40	70	0.100	02	20
B	MECH	14.7	72	-297	0.070	59	100
B	PNEU	1500		70		0	40
B	PNEU	1500		70	0.039	0	40
Z	MECH	1500	72	70	0.040	2	07
X	PNEU	1500		72	0.060	1	87
I	MECH	2000	72	70		1	1
X	PNEU	2000		70		2	137
X	PNEU	2000		70	0.082	4	59
X	PNEU	2000		72	0.060	1	45
B	MECH	250	72	70	0.077	02	07
I	MECH	3000	72	70		1	1
X	PNEU	3000		70	0.062	5	108
X	PNEU	3000		72	0.062	5	174
C	MECH	3000	72	72	0.102	0	40
B	PNEU	3500		70	0.100	0	20
X	PNEU	3500		72	0.062	9	117
X	PNEU	4000		72	0.062	9	205
X	PNEU	4500		72	0.062	13	192
B	PNEU	500		250	0.073	0	20
B	MECH	500	72	70		0	20
B	MECH	500	72	70	0.040	2	11
B	PNEU	500		70	0.052	0	40
B	MECH	500	10	70	0.077	0	20
B	PNEU	500		70	0.082	0	20
X	PNEU	5000		72	0.062	15	134
X	PNEU	5500		70	0.073	3	73
X	PNEU	6000		70	0.073	7	37
B	PNEU	65		250	0.071	0	180
B	MECH	65	72	250	0.072	0	40
X	PNEU	6500		70	0.117	1	02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.30	.03	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	20.615	

65027 RUBBER VITON GF CPD SEE REPORT GID: DODFXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
S	HYZE
S	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63405 RUBBER VITON MDAC 18210-16

MANF: MCDONNELL DOUGLAS SPEC: MIL-R-83248T2C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.057			03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006488 7

63405 RUBBER VITON MDAC 18210-16 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00180.30	

20717 RUBBER VITON NE8477 GID: CHDPXX

MANF: LORD CORP

SPEC: MIL-R-83248T1C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	1050	72	70	0.080	0	20
X	PNEU	1050		70	0.080	1	20
C	MECH	3670	72	70	0.080	0	20
B	PNEU	500		70	0.080	0	20
C	MECH	7400	25	70	0.080	00	20

62856 RUBBER VITON O-RING GID: DOXXXX

MANF: ADTECH
C E CONOVER
NUPRO COMPANY
PARKER SEAL

SPEC: AS180-022

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.086	2	02
B	MECH	14.7	72	-297	0.135	0	20
B	PNEU	3000		68	0.102	0	20
B	PNEU	5000		72	0.062	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.12	.61	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

65176 RUBBER VITON O-RING 19357 GID: CHDEXX

MANF: TECHNICAL SALES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	400	10	-297	0.012	1	01

69924 RUBBER VITON O-RING 2-904

MANF: MOSS SEAL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1115	72	77	0.074	00	20

65109 RUBBER VITON O-RING CPD 16129 GID: DOXXXX

MANF: TECHNICAL SALES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297		1	01

65108 RUBBER VITON O-RING CPD 16207 GID: DOXXXX

MANF: TECHNICAL SALES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297		1	01

65174 RUBBER VITON O-RING CPD 19447 GID: DOXXXX

MANF: TECHNICAL SALES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.070	1	01

MSFC-HDBK-527 REV F 9999942 0006489 9

Information Handling Services, 2000

65465 RUBBER VITON O-RING S/A 2-012 GID: DODEXX

MANF: PARKER SEAL — SPEC: MIL-R-83248T1C — MIL-R-83248T1C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.070	01	06
B	MECH	230	72	70	0.070	00	20
C	MECH	230	45	70	0.070	00	20

65466 RUBBER VITON O-RING S/A 2-014 GID: DODEXX

MANF: PARKER SEAL — SPEC: MIL-R-83248T1C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.070	01	04
B	MECH	230	72	70	0.070	01	60

65464 RUBBER VITON O-RING S/A 2-016 GID: DODEXX

MANF: PARKER SEAL — SPEC: MIL-R-83248T1C — MIL-R-83248T1C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.070	01	01
B	MECH	230	72	70	0.070	00	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.24	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65467 RUBBER VITON O-RING S/A 2-020 GID: DODEXX

MANF: PARKER SEAL — SPEC: MIL-R-83248T1C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.070	01	07
B	MECH	230	72	70	0.070	00	20

65463 RUBBER VITON O-RING S/A 2-024 GID: DODEXX

MANF: PARKER SEAL — SPEC: MIL-R-83248T1C

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.070	01	01
B	MECH	230	72	70	0.070	01	60

65468 RUBBER VITON O-RING S/A 2-035 GID: DODEXX

MANF: PARKER SEAL — SPEC: MIL-R-83248T1C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	15	-297	0.070	01	04
X	MECH	230	10	-297	0.070	00	20
B	MECH	230	72	70	0.070	00	20

65390 RUBBER VITON O-RING S/A 2-212 GID: DOXXXX

MANF: PARKER HANNIFIN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	400	72	-297		1	1

65430 RUBBER VITON O-RING S/A 2-343 GID: DODEXX

MANF: PARKER SEAL — SPEC: MIL-R-83248T1C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.210	01	06

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006490 5

65430 RUBBER VITON O-RING S/A 2-343 (cont)

FLAMMABILITY								FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
											B	MECH	230	72	70	0.210	00	20

65182 RUBBER VITON O-RING S/A2-214 GID: DOXXXX
MANF: PARKER HANNIFIN

FLAMMABILITY								FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		X	MECH	400	10	-297	0.140	1	1

65090 RUBBER VITON O-RING V730-75 GID: CHDEXX
MANF: PARKER SEAL

FLAMMABILITY								FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		X	MECH	14.7	10	-297		1	01

65091 RUBBER VITON O-RING V835-75 GID: DODEXX
MANF: ADVANCE SEAL

FLAMMABILITY								FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		X	MECH	14.7	10	-297		1	01

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	3.0E-6	.76	.02	.30	

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
No test data			

80244 RUBBER VITON O-RING V909-90 GID: DOXXXX

FLAMMABILITY								FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	PNEU	3100		75	0.072	00	20
											X	PNEU	3600		75	0.072	01	14
											X	PNEU	6600		75	0.072	01	04

05151 RUBBER VITON PLV2000 GID: DODEXX
MANF: PELMOR LABORATORIES

FLAMMABILITY								FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.012			02.90	SMALL	No test data		B	PNEU	1000		70	0.011	0	20
											X	PNEU	1500		70	0.011	01	20
											X	PNEU	1500		70	0.011	1	20
											Z	MECH	1500	72	70	0.011	01	09

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.00	.63	.00	36H-77F- 1H-300F-

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	X	00001.90	24H-150F-

63039 RUBBER VITON RA61375VC GID: DODEXX
MANF: EH33

FLAMMABILITY								FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.075		00.00	00.00	NONE	No test data		No test data							

61597 RUBBER VITON SHORE A GID: DVDEXX
MANF: BRIGGS RUBBER PROD SPEC: ST61V776

FLAMMABILITY								FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	025.9	014.3	0.034			00.90	SMALL	No test data		No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006491 7

61597 RUBBER VITON SHORE A (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	033.0	014.3	0.034		00.09	08.50	MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.2E-6	.17	.00		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.59	

65181 RUBBER VITON SR2702-72 GID: DOXXXX

MANF: SARGENT INDUSTRIES SPEC: MIL-R-83248A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	400	10	-297		1	01

62275 RUBBER VITON V14 GID: DODEXX

MANF: C & C PACKINGS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70		0	20
X	PNEU	1500		70		1	10
X	PNEU	2000		70		2	14
X	PNEU	3000		70		2	07
B	PNEU	3500		70	0.070	0	60
X	PNEU	4000		70	0.070	6	23
X	PNEU	5000		70	0.101	4	20
X	PNEU	6000		70	0.101	2	06

20345 RUBBER VITON V2-5159 GID: DODEXX

....NO TEST DATA AVAILABLE....

61284 RUBBER VITON V672-7 GID: DOCHXX

MANF: PARKER SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	PNEU	4000		70	0.080	00	03
B	PNEU	4500		70	0.080	00	20
X	PNEU	5000		70	0.080	1	05

62872 RUBBER VITON V709-9 GID: CHDEXX

MANF: TECHNICAL SALES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	72	-220	0.067	0	40

61627 RUBBER VITON V709-90 GID: DOXXXX

MANF: PARKER SEAL SPEC: MIL-R-83248 MIL-R-83248T1C2
MIL-R-83248T2C2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	-297	0.117	1	60
Z	MECH	14.7	72	-297	0.117	1	20
B	MECH	1500	72	-297	0.117	1	60
B	PNEU	2100		70	0.070	0	20
X	PNEU	2500		70	0.070	1	03
Z	MECH	2500	72	70	0.117	1	03
Z	MECH	3000	72	70	0.117	1	01
B	PNEU	4500		70	0.087	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006492 9

61627 RUBBER VITON V709-90 (cont)

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
											B	MECH	500	72	-297	0.117	0	20
											B	MECH	500	72	70	0.117	0	20
											X	PNEU	5000		70	0.087	1	20
											B	PNEU	5000		70	0.110	0	20
											X	PNEU	5500		70	0.087	2	40
											B	PNEU	6000		70	0.072	0	20
											B	PNEU	6000		70	0.072	4	25
											X	PNEU	6000		70	0.087	0	20
											X	PNEU	6000		70	0.087	4	25
											X	MECH	6000	15	70	0.087	2	08

62201 RUBBER VITON V747-7 GID: CHDEXX

MANF: FLODYNE CONTROLS
TECHNICAL SALES

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		I	PNEU	1500		70		0	09
											X	PNEU	2000		70		2	23
											X	PNEU	3000		70		1	39
											C	MECH	3000	25	72	0.069	0	20
											X	PNEU	3500		70		3	51
											B	MECH	400	72	-220	0.067	0	20
											B	MECH	400	72	-220	0.115	0	20
											X	PNEU	4000		70		8	38
											X	PNEU	5000		70		4	08
											X	PNEU	6000		70		2	04
											X	PNEU	7000		70		2	02
											X	PNEU	8000		70		1	01
											X	PNEU	9000		70		1	01

60643 RUBBER VITON V747-75 GID: CHDEXX

MANF: DRAGON VALVES INC
MILLER
PARKER HANNIFIN
PARKER SEAL
TECHNICAL SALES

SPEC: M83248/1-025
MIL-R-83248
MIL-R-83248T1C1
MIL-R83248/1904
M83248/1-026
MIL-R-83248C1T1
MIL-R-83248T1CT

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	PNEU	1000		70	0.057	0	20
											B	PNEU	1000		70	0.057	0	70
											Z	MECH	1000	72	70	0.070	2	11
											C	MECH	1050	35	70	0.070	0	20
											Z	MECH	14.7	72	-297	0.070	8	20
											X	PNEU	1500		70	0.066	3	76
											X	PNEU	2000		70	0.066	11	202
											Z	MECH	2000	72	70	0.066	2	2
											X	PNEU	2500		70	0.066	10	172
											Z	MECH	2500	72	70	0.066	1	1
											X	PNEU	3000		70		1	08
											X	PNEU	3000		70	0.066	14	192
											Z	MECH	3000	72	70	0.066	2	15
											X	PNEU	3500		70	0.066	19	167
											B	MECH	400	72	-220	0.062	0	20
											B	MECH	400	72	-220	0.090	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006493 0

60643 RUBBER VITON V747-75 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	72	-220	0.100	0	20
B	MECH	400	72	-220	0.137	0	20
B	MECH	400	72	-220	0.140	0	20
X	PNEU	4000		70	0.066	08	195
X	PNEU	4000		70	0.066	8	195
Z	MECH	4000	72	70	0.066	1	2
I	MECH	4500	72	70	0.066	1	2
X	PNEU	4500		70	0.066	10	117
B	MECH	500	72	70	0.066	0	20
X	PNEU	5000		70		1	01
X	PNEU	5000		70	0.066	14	96
X	MECH	5500	10	70	0.062	0	20
X	PNEU	5500		70	0.066	08	59
X	PNEU	5500		70	0.066	8	59
X	PNEU	6000		70	0.066	09	78
X	PNEU	6000		70	0.066	9	78
X	MECH	6000	10	70	0.070	0	20
X	PNEU	7000		70	0.071	03	10
X	PNEU	7000		70	0.071	3	10
X	PNEU	8000		70	0.071	04	09
X	PNEU	8000		70	0.071	4	09
X	PNEU	9000		70	0.071	02	08
X	PNEU	9000		70	0.071	2	08

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.14	.05	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61880 RUBBER VITON V763-60 GID: CHDEXX

MANF: PARKER SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70	0.062	0	20
X	PNEU	2000		70	0.062	01	10

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.1E-6	.14	.00		

ODOR

RT	RT WEIGHT	CURE
A	A 00009.05	

TOXICITY

61879 RUBBER VITON V769-60 GID: CHDEXX

MANF: PARKER SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.062	0	02
X	PNEU	1500		70	0.062	0	16
X	PNEU	2000		70	0.062	1	08
X	PNEU	2500		70	0.062	01	04
X	PNEU	2500		70	0.062	1	04

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.1E-6	.20	.00		

ODOR

RT	RT WEIGHT	CURE
A	V 00010.05	

TOXICITY

05320 RUBBER VITON V77 GID: CHDEXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70	0.001	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006494 2

05320 RUBBER VITON V77 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70	0.001	00	20
Z	MECH	1500	72	70	0.062	1	3

61123 RUBBER VITON V779-75 GID: CODEXX
MANF: PARKER SEAL
SPEC: AMS 7276

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	250	72	70	0.049	0	20
B	PNEU	500		250	0.039	0	20
B	PNEU	500		250	0.049	0	20
B	PNEU	500		70	0.049	0	20
B	MECH	500	72	70	0.049	1	60

20151 RUBBER VITON V80-080/CHR 985 GID: DODFXX
MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.092			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1500	35	70	0.092	0	20
X	PNEU	1500		70	0.092	1	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.25	

TOXICITY

61261 RUBBER VITON V884-75 GID: CHDEXX
MANF: MILLER
PARKER HANNIFIN
PARKER SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	2500		70		0	20
I	PNEU	3000		70		1	05
X	MECH	400	10	-297		1	1
X	PNEU	4000		70		1	02
X	PNEU	5000		70		1	01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.4E-6	.22	.00	.10	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

61266 RUBBER VITON V894-90 GID: CHDEXX
MANF: PARKER SEAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.4E-6	.17	.04	.07	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

62320 RUBBER VITON VD000B GID: DOXXXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1000		70	0.026	0	20
X	PNEU	1500		70	0.026	1	05
X	PNEU	2000		70	0.026	2	03
X	PNEU	3000		70	0.026	1	02

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006495 4

61598 RUBBER VITON VL1502-H141 GID: DODEXX
MANF: VERNAY LABORATORIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	68	0.065	2	52
B	PNEU	1000		70	0.065	0	20
B	PNEU	135		250	0.064	0	180
B	MECH	135	72	250	0.073	0	140
B	MECH	1500	65	68	0.065	0	20
B	MECH	1500	72	68	0.065	1	20
X	PNEU	1500		70	0.065	2	07
B	MECH	250	72	68	0.065	0	20

65056 RUBBER VITON VL1502H285 GID: DODEXX
MANF: VERNAY LABORATORIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.14	.04	.05	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00029.00	

65317 RUBBER VITON VL1502H285 GID: DODEXX
MANF: VERNAY LABORATORIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	009.0				01.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

83157 RUBBER VULCON CL 1 GR 40 T2 SPEC: MIL-R-25988B
MANF: TECKNIT
....NO TEST DATA AVAILABLE....

83159 RUBBER VULCON CL 2 GR 40 SPEC: ZZ-R-765
MANF: TECKNIT
....NO TEST DATA AVAILABLE....

83158 RUBBER VULCON SILICONE
MANF: TECKNIT
....NO TEST DATA AVAILABLE....

20757 SAFETY WALK RESIN P/S CORK/RUB
....NO TEST DATA AVAILABLE....

65266 SALOX-M GID: BBCOXX
MANF: ALLEGHENY PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	600	10	-297	0.090	0	20
I	MECH	600	10	575	0.090	0	20

20765 SANITIZER AMMONIUM STERICIDE GID: BVFCXX
MANF: PENNWALT CORP SPEC: ST80S589 ST80S589-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003	00.00	00.00	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.0E-7	39.96	.24		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00019.83	24H-70F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006496 6

20228 SAPPHIRE
MANF: WOLFF ENGINEERING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.002			04.30	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.43	.07	.01	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20417 SCREEN NYLON MESH GID: BFBVXX
MANF: MENARDI-SOUTHERN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.041		00.28	12.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
A	K 00020.21	

TOXICITY

62073 SCREEN POLYESTER/PVC COATED MESH GID: BLCBXX
MANF: ADVANCED NETTING SPEC: ST11M039

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.011		00.24	12.00	T MOD
X	1	025.9	014.3	0.011		01.33	12.00	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.6E-7	19.61	13.53		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
	K 00009.82	

TOXICITY

61922 SCREEN TEFLON FEP/FIBERGLASS GID: COBOFV
MANF: COMMERCIAL KANES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.032			01.40	NONE
A	1	025.9	014.3	0.021			01.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63968 SEALANT 15% GLASS FILLED TFE GID: DQIAXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.060	0	20
X	MECH	4500	20	-297	0.060	0	20
B	PNEU	5000		72	0.060	0	20

63967 SEALANT 25% GLASS FILLED TFE GID: DQIAXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.060	0	20
C	MECH	4500	30	-297	0.060	0	20
B	PNEU	4500		72	0.060	0	20
B	PNEU	5000		72	0.060	0	20

05463 SEALANT 905 EPOXY GID: DPBGXX
MANF: LEAR SIEGLER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.006	0.003		04.20	NONE
A	1	030.0	009.0	0.007	0.003		05.00	SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
A	B 00015.15	3H-300F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006497 8

63163 SEALANT AIR-O-SEAL GID: DPXXXX
MANF: ARI INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001			01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20276 SEALANT BARCO THERMOSET GID: DPXXXX
MANF: BARWOOD MFG
SPEC: RS-128585-SS-3 RS-99450-SS-3

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	7.8E-7	25.75	11.00		

ODOR

RT	RT	WEIGHT	CURE
A	K	00004.32	.

TOXICITY

05175 SEALANT CARBON BASE FACE F658RC GID: CHXXXX
....NO TEST DATA AVAILABLE....

20061 SEALANT CARBON PLUS BINDER P4229 GID: CHXXXX
MANF: PURE CARBON
....NO TEST DATA AVAILABLE....

20062 SEALANT CDJ83 CARBON PLUS BINDER GID: CHXXXX
MANF: UNION CARBIDE
....NO TEST DATA AVAILABLE....

05101 SEALANT CERAMIC G/I88 1/4 BAKE
....NO TEST DATA AVAILABLE....

62912 SEALANT CIRCLE P/N 32834 GID: CHXXXV
MANF: CIRCLE SEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-220	0.106	0	20

05721 SEALANT COLAD 984 A/B GID: AWBGXX
MANF: COLGATE-PALMOLIVE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.098	0.003		00.20	NONE
C	1	023.8	014.5	0.098	0.003	00.09	12.00 T	SMALL
C	2	030.0	010.0	0.009	0.003	00.00	00.00	NONE
C	1	030.0	010.0	0.009	0.003	00.35	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.84	.01	.00	16H-212F-

ODOR

RT	RT	WEIGHT	CURE
A	V	00023.14	168H-70F- 24H-150F-

TOXICITY

05279 SEALANT CYANOSILICONE PRP711 GID: DPCKXX
MANF: PROD RESEARCH & CHEM
SPEC: MB0130-131

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.003		00.00	00.00	NONE
A	1	023.8	014.5	0.003			02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.02	.52	.00	

ODOR

RT	RT	WEIGHT	CURE
A	X	00019.90	.

TOXICITY

62911 SEALANT DIRECT SHAFT CARBON G84 GID: CHFOXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	50	72	-297		2	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006498 T

62911 SEALANT DIRECT SHAFT CARBON G84 (cont)

FLAMMABILITY									FSC		OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
											B	MECH	50	72	68		0	20

60824 SEALANT DUXSEAL GID: DPXXXX
MANF: JOHNS-MANVILLE

FLAMMABILITY									FSC		OXYGEN COMP							
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.100	0.003		00.60	NONE	A	HYZE	No test data							
B	1	033.0	014.3	0.100	0.003		07.00	NONE	C	HYZE								
									A	MMH								
									C	MMH								
									C	N2O4								

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	3.58	1.60			A	V 00020.16	

05315 SEALANT EPOXY CORROSION INHIBITOR 71-Y-1 GID: DPBGXX
MANF: DEFT SPEC: NAI-1328B

FLAMMABILITY									FSC		OXYGEN COMP							
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	030.0	009.0	0.003	0.003	00.94	12.00	T MOD	No test data		No test data							

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	3.7E-6	6.10	.57				X 00022.56	

20075 SEALANT EPOXY HARD FILTER GID: DPBGXX
MANF: BENDIX
....NO TEST DATA AVAILABLE....

61681 SEALANT FLUOROCARBON M83248/2-916 GID: CHDEDE
MANF: SARGENT INDUSTRIES SPEC: MIL-R-83248T1C1 MIL-R-83248T1C2

FLAMMABILITY									FSC		OXYGEN COMP							
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		B	MECH	14.7	72	-297		2	03
											B	MECH	1500	72	-297		0	40
											Z	MECH	500	72	70		2	18
											C	MECH	6000	25	70		0	20

61680 SEALANT FLUOROCARBON MS832 18/2-904 GID: CHDEDE
MANF: SARGENT INDUSTRIES SPEC: MIL-R-83248T1C1 MIL-R-83248T1C2

FLAMMABILITY									FSC		OXYGEN COMP							
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		Z	MECH	1000	72	70		02	11
											Z	MECH	14.7	72	-297		2	2
											B	MECH	1500	72	-297		00	20
											I	MECH	1500	72	70		0	08
											B	MECH	500	72	70		00	20
											X	MECH	6000	10	70		1	20

61055 SEALANT FOMOFIX POLYURETHANE GID: DPCQXX
MANF: FOMO PRODUCTS

FLAMMABILITY									FSC		OXYGEN COMP							
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	012.4	0.500			02.70	NONE	No test data		No test data							
B	1	030.0	009.0	1.000			07.30	NONE										

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006499 1

61055 SEALANT FOMOFIX POLYURETHANE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	TOXICITY RT	WEIGHT	CURE
	X	00009.92	

06324 SEALANT FRAYCHECK GID: DPXXXX

MANF: GENERAL DISPERSION

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		01.70	NONE
A	1	033.0	014.3	0.001	0.003		02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	TOXICITY RT	WEIGHT	CURE
	X	00000.32	1H-70F- 168H-70F-

61130 SEALANT GAGEKOTE 3 SILICONE GID: DPCKXX

MANF: W T BEAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.011	0.003		02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	5.2E-7	4.28	2.80		24H-70F- 24H-150F-

ODOR

RT	TOXICITY RT	WEIGHT	CURE
No test data			

65397 SEALANT GASK-O-SEAL GID: DQXXXX

MANF: PARKER SEAL

....NO TEST DATA AVAILABLE....

63764 SEALANT GRAPHITAR 114/CARBON

MANF: U S GRAPHITE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.250	0	20
B	MECH	14.7	72	-297	0.578	0	20
B	MECH	300	72	-297	0.250	0	20
B	MECH	300	72	-297	0.578	0	20

05244 SEALANT GRAPHITAR 39/CARBON FACE GID: DPXXXX

MANF: U S GRAPHITE

....NO TEST DATA AVAILABLE....

20015 SEALANT GRAPHITAR 86/CARBON GID: CHGFFO

MANF: U S GRAPHITE

....NO TEST DATA AVAILABLE....

61263 SEALANT GRAPHITE FILLED TEFLON GID: FICNGF

MANF: ROYAL INDUSTRIES

....NO TEST DATA AVAILABLE....

05562 SEALANT GRAPHITE PUREBON P5N GID: DPEHXX

....NO TEST DATA AVAILABLE....

05412 SEALANT GRAPHITE PYROLITIC GID: DPEHXX

SPEC: MB0115-010

MANF:

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006500 4

62826 SEALANT GS1450 POURABLE GID: DRXXXX
MANF: GROVE SPECIALTIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	72	-297	0.050	15	20

61365 SEALANT KOPR-SHIELD GID: DPHNXX
MANF: JET-LUBE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.3E-6	65.63	20.00		24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00004.73	24H-150F-

00133 SEALANT LOX-SAFE GID: DPXXXX
MANF: ARMITE LABS
SPEC: MB0140-001

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.6E-6	78.50	7.50		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00008.33	

05290 SEALANT METASEAL 19V5M POLYESTER GID: DPCBXX
MANF: AMERICAN METASEAL CO
CLARK INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	9.39	.50	.00	3H-300F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

20192 SEALANT MICROSEAL GID: DPXXXX
MANF: MICROSEAL CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.10	.01	.00	720H-70F-
					96H-212F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00000.48	168H-70F-
		24H-150F-

05918 SEALANT NEOPRENE DAPCO 2030 GID: FJDBXX
MANF: D AIRCRAFT PRODUCTS
SPEC: MB0120-065

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.005	0.003		01.30	NONE
A	1	023.8	014.5	0.004			01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	15	-297	0.005	01	12
C	MECH	14.7	45	-314	0.005	00	20
B	MECH	50	72	-150	0.005	00	20
C	MECH	50	45	70	0.005	00	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.81	.02		192H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00021.13	24H-150F-

80019 SEALANT OXY-TITE WITH TEFLON THREAD GID: DSXXXX
MANF: LAKE CHEMICAL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.050	00	20
B	MECH	275	72	80	0.050	00	20
B	MECH	50	72	80	0.050	00	20

06184 SEALANT PLENUM SHELL CVR POLYURETHANE GID: DPCQXX
MANF: SHELL CHEMICAL
....NO TEST DATA AVAILABLE.....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006501 6

61710 SEALANT POLYESTER GID: DQCBXX
MANF: 3M CO SPEC: MB0125-048

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.2E-6	2.81	.09		24H-70F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	X	00002.07	24H-70F-

05861 SEALANT POLYSULFIDE 1221B-2 GID: DPCIXX
MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.013	0.003	00.00	00.00	NONE
C	1	023.8	014.5	0.013	0.003	00.65	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	57.39	2.90	.00	48H-70F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	B	00027.98	48H-70F- 24H-150F-

20473 SEALANT POLYSULFIDE EC101 GID: DPDLXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

69795 SEALANT POLYSULFIDE PR1201 RLS
MANF: PROD RESEARCH & CHEM
....NO TEST DATA AVAILABLE....

20527 SEALANT POLYSULFIDE PR1201HT GID: DPDXXX
MANF: PROD RESEARCH & CHEM SPEC: ST34C749

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.083			10.60	NONE
C	1	025.9	014.3	0.083		00.36	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	33.23	1.48	.00	24H-70F- 24H-150F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	X	00020.21	24H-70F- 24H-150F-

60056 SEALANT POLYSULFIDE PR1422 GID: DPDLXV
MANF: PROD RESEARCH & CHEM SPEC: 10A00527 P1.0 MIL-S-8802

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.125		00.00	00.00	NONE
C	1	020.9	014.7	0.125		00.06	12.00	T NONE
I	1	020.9	014.7	0.074		00.02	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.69	.56	.62	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

05878 SEALANT POLYSULFIDE PR1750B GID: BADLXX
MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.096	0.020	00.02	12.00	T NONE
C	2	023.8	014.5	0.016	0.003	00.00	00.00	NONE
C	1	023.8	014.5	0.016	0.003	00.33	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.99	.16	.00	168H-70F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
X	B	00035.06	168H-70F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006502 8

05878 SEALANT POLYSULFIDE PR1750B (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					24H-150F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
		24H-150F-

85428 SEALANT POLYSULFIDE PR1770 GID: BADLXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	00.09	0.020	00.03	7.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85432 SEALANT POLYSULFIDE PR1770 FR GID: BADLXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.0	014.7	0.105	0.020	00.04	02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61928 SEALANT POLYSULFIDE PR385M GID: DRDLXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	020.9	014.7	0.002	0.003	00.00	00.00	NONE
I	1	020.9	014.7	0.002	0.003		07.10	NONE
C	2	025.9	014.3	0.002	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.002	0.003	00.84	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.0E-7	1.25	48.20	2.04	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

20074 SEALANT POLYSULFIDE PROSEAL 890 GID: DPDLXX

MANF: COAST PROSEAL SPEC: MIL-S-8802

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.73	.15	2.60	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05639 SEALANT POLYSULFIDE PRP1436 GID: DPDLXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.023	0.003	00.00	00.00	NONE
C	1	023.8	014.5	0.023	0.003	00.22	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	B 00162.13	168H-70F-
		24H-150F-

20528 SEALANT POLYURETHANE PR1656 GID: DPCQXX

MANF: PROD RESEARCH & CHEM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.127			01.50	NONE
X	1	025.9	014.3	0.127		00.18	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.8E-6	.91	.09	.00	1H-150F-
					24H-135F-

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 00020.01	4H-130F-

MSFC-HDBK-527 REV F 9999942 0006503 T

Information Handling Services, 2000

63716 SEALANT POLYURETHANE PR1660 GID: DPCQXX
MANF: PROD RESEARCH & CHEM SPEC: MB0130-130

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.005		00.29	05.23	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.42	.01	.00	24H-150F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05214 SEALANT POLYURETHANE PRP1600 GID: DPCQXX
MANF: PROD RESEARCH & CHEM SPEC: MB0130-136

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.86	.61		16H-212F-

ODOR

RT	RT	WEIGHT	CURE
A	B	00039.04	144H-70F-

TOXICITY

05785 SEALANT PROSEAL 247A/B URETH GID: DPCQXX
MANF: COAST PROSEAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.006		00.00	00.00	NONE
C	1	023.8	014.5	0.006		00.30	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.4E-6	38.67	1.59		24H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	X	00017.50	24H-70F-

TOXICITY

05818 SEALANT PROSEAL 727-2-3 POLYSULFIDE GID: DPDLXX
MANF: ESSEX CHEM CORP SPEC: MIL-S-8516ET2C3

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	V	00006.27	16H-70F-
			16H-176F-

TOXICITY

60393 SEALANT PROSEAL 870 GID: DPXXXX
....NO TEST DATA AVAILABLE....

20068 SEALANT PUTTY 453 5 K36 BLK GID: DPAHXX
MANF: GLIDDEN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	B	00029.13	24H-70F-
			24H-150F-

TOXICITY

62039 SEALANT RUBBER 27980 GID: CHHDXX
MANF: C E CONOVER SPEC: MIL-R-5315

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.120			01.10	NONE
C	1	025.9	014.3	0.120		00.13	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-6	8.61	4.63		

ODOR

RT	RT	WEIGHT	CURE
X	X	00020.23	

TOXICITY

05349 SEALANT SCOTCHSEAL 3950 GID: DPAKXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002			02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006504 1

05349 SEALANT SCOTCHSEAL 3950 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.002	0.003	00.00	00.00	NONE
C	1	030.0	010.0	0.002	0.003	00.40	12.00	T SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.6E-6	10.24	.02		2.5H-75F- 1H-250F-

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00001.28	SEE TVS CURE1

20402 SEALANT SCOTCHSEAL EC1103 GID: ABCKXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.016	0.003	00.07	12.00	T NONE
C	1	025.9	014.3	0.016	0.003	00.95	12.00	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	11.42	.00		24H-70F- 24H-150F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00022.31	24H-70F- 24H-150F-

85434 SEALANT SIL-PAD K10 INSULATOR KAPTON XT POLYIMIDE FILM WITH BORON NITRIDE FILLED SILICONE RUBBER GID: DPXXXX

MANF: BERGQUIST SPEC: MIL-M-38527/8A-001-P

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	0.006		00.18	12.0	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85437 SEALANT SIL-PAD K4 INSULATOR RUBBER WITH KAPTON XT FILM

MANF: BERGQUIST SPEC: MIL-M-38527/8A-001-P

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	0.006		00.22	11.0	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61961 SEALANT SILICONE GID: DPCKXX

MANF: ITT CANNON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-7	.56	.04		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

63323 SEALANT SILICONE CARBIDE GID: CHCKFO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	500	72	-220	0.053	1	10

60614 SEALANT SILICONE HIGH VACUUM GID: DPCKXX

....NO TEST DATA AVAILABLE....

80045 SEALANT SILICONE KE348 GID: DPCKXX

MANF: SHIN-ETSU CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	024.5	014.5	0.130	0.003		04.40	NONE
C	1	024.5	014.5	0.130	0.003	00.15	12.00	T SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	22.657	16H-70F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006505 3

80178 SEALANT SILICONE KE44

MANF: SHIN-ETSU CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.290		0.02	11.80	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	22.251	216H-70F-

61973 SEALANT SILICONE SIL-PADS 400 GID: DPCKXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.009			03.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.45	.14	.43	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00006.79	

05377 SEALANT SILICONE/DACRON HAVEG F717/720 GID: DPCBXX

MANF: HAVEG SPEC: AMS 3302

....NO TEST DATA AVAILABLE....

06299 SEALANT SILICONE/FEP TEFLON GID: CHDPCN

MANF: RUBBER SPECIALTIES SPEC: ZZ-R-765 CL 3B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.200		00.01	08.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05738 SEALANT SILICONE/NOMEX HT-5 GID: DPCKXX

....NO TEST DATA AVAILABLE....

05170 SEALANT SILICONE/NOMEX HT2002 GID: DPCKBS

MANF: HASKON CORPORATION
HERCULES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.065			00.10	NONE
A	1	023.8	014.5	0.065			02.80	NONE
X	1	030.0	010.0	0.072		00.07	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.2E-6	.09	.01		16H-480F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00021.80	

63919 SEALANT SPIRASEAL METAL/TFE GID: CHXXXX

MANF: LAMONS METAL GASKET

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.075	0	20
B	MECH	300	72	-297	0.075	0	20
X	PNEU	4500			0.021	02	14

06041 SEALANT SYNKOLOID VINYL SPACKL GID: DPXXXX

....NO TEST DATA AVAILABLE....

62177 SEALANT TEFLON NOC GID: DPCNXX

MANF: TESCOM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	3000		70	0.037	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006506 5

62177 SEALANT TEFLON NOC (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	3500		70	0.037	2	40
I	PNEU	4000		70	0.069	0	05
B	PNEU	4500		70	0.034	0	20
X	PNEU	4500		70	0.034	2	03
B	PNEU	4500		70	0.069	0	20
X	PNEU	5000		70	0.037	4	49
X	PNEU	6000		70	0.069	1	05

62154 SEALANT TEFLON TFE O-RING GID: CHCOXX

MANF: DODGE WASMUND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	10000	72	300	0.137	2	16
B	MECH	6000	72	300	0.137	0	02
B	MECH	7000	72	300	0.137	0	02
B	MECH	8000	72	300	0.137	0	02
B	MECH	9000	72	300	0.137	0	02

05471 SEALANT TFE/GL/MOS2 J114-7-2F-GM GID: CHCNEJ

....NO TEST DATA AVAILABLE....

20405 SEALANT THREAD LOCKING

MANF:

SPEC: MIL-S-46163

....NO TEST DATA AVAILABLE....

85491 SEALANT THREAD LOCKING COMPOUND

MANF: AQM

SPEC: MIL-S-46163 T2 GR W

....NO TEST DATA AVAILABLE....

20054 SEALANT THREAD VC3 GID: DPBGXX

MANF: NYLOK-DETROIT CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		02.20	NONE

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.99	.69	.00	1H-165F- 1H-249F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00002.94	168H-70F-

60383 SEALANT TORQUE F900 GID: CHXXXX

MANF: ORGANIC PRODUCTS

SPEC: USBI99621-0001

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.040		00.75	12.00	T MOD

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	13.78	1.30	.00	.4H-46F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00005.98	

06381 SEALANT TORR EPOXY 953-001 GID: CHBGXX

MANF: VARIAN ASSOCIATES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	100	72	70	0.016	0	20
B	PNEU	250		70	0.013	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006507 7

06381 SEALANT TORR EPOXY 953-001 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	250	72	70	0.016	2	13

62195 SEALANT TRIBOLON PI101 POLYIMIDE GID: CHCDXX

MANF: TRIBOL INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70	0.058	0	20
X	PNEU	2000		70	0.058	2	13

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	9.0E-7	1.83	.00		

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

60241 SEALANT UF3119 GID: DPXXXX

MANF: SPEC: STW5-2998

....NO TEST DATA AVAILABLE....

60240 SEALANT UF3177 GID: DPXXXX

MANF: SPEC: STW5-2997

....NO TEST DATA AVAILABLE....

60121 SEALANT UF3195

MANF: THIOKOL SPEC: STW5-2678

....NO TEST DATA AVAILABLE....

63191 SEALANT URETHANE S183026 GID: DPCQXX

MANF: HYSOL/DEXTER SPEC: EP1664M

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.004	0.003		02.10	NONE

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

62241 SEALANT VANWAY FEP TEFLON O-RING GID: DPBOCO

MANF: A W CHESTERTON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME
A	MMH
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

20731 SEALANT VIBRA-TITE ADHESIVE GID: DPXXXX

MANF: OAKLAND CORPORATION

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.008	0.003	00.00	00.00	NONE
B	1	025.9	014.3	0.008	0.003		07.80	NONE

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.37	.14	.00	24H-70F-

ODOR

RT	RT WEIGHT	CURE
A	X 00020.68	24H-70F-

TOXICITY

61150 SEALANT VITON AP2709 GID: DPDEXX

MANF: ARROWHEAD PRODUCTS SPEC: MIL-R-83248

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.8E-6	2.97	1.15		

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006508 9

80134 SEALANT WEATHERBAN 101 POLYSULFIDE GID: DPDLXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.127		00.09	07.00	NONE
C	1	030.0	010.0	0.158		00.20	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	7.0E-6	37.62	.87	.41	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	22.257	

61268 SEALANT ZINC CHROMATE GRAY GID: DPAHXX

MANF: RANDOLPH PRODUCTS SPEC: MIL-P-8116

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00041.11	24H-70F- 24H-150F-

61129 SEALANT ZINC/GREASE 21059 GID: DPHAXX

MANF: THOMAS & BETTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.3E-6	5.13	2.39		24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00021.11	24H-150F-

61956 SEALS K-6 LEAD COATED GID: CHMPXX

MANF: HARRISON MFG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1050	72	540	0.110	02	02
B	MECH	14.7	15	-297	0.114	0	01
B	PNEU	3300		190	0.055	0	20
B	MECH	3300	72	190	0.110	02	02
B	MECH	3300	30	190	0.111	1	05

64131 SEALS PTFE KC103-10

....NO TEST DATA AVAILABLE....

64132 SEALS PTFE KC103-12

....NO TEST DATA AVAILABLE....

64134 SEALS PTFE KC103-16

....NO TEST DATA AVAILABLE....

64133 SEALS PTFE KC103-20

....NO TEST DATA AVAILABLE....

64135 SEALS PTFE KC103-24

....NO TEST DATA AVAILABLE....

64128 SEALS PTFE KC103-4

....NO TEST DATA AVAILABLE....

64129 SEALS PTFE KC103-6

....NO TEST DATA AVAILABLE....

64130 SEALS PTFE KC103-8

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006509 0

20682 SHAVER WIND-UP 122A

....NO TEST DATA AVAILABLE....

65425 SHAVING CREME GEL 5951 D68B

MANF: JOHNSON & JOHNSON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00127.74	

TOXICITY

20018 SHELL 405 CATALYST

MANF: SHELL CHEMICAL

....NO TEST DATA AVAILABLE....

62472 SHIELD POLYCARBONATE PLASTIC GID: DLCAXX

MANF: SCOTT AVIATION SPEC: NAS-9-15246

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.083			00.20	NONE
X	1	023.8	014.5	0.083			04.40	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60887 SHIELD RADIATION GID: FJCNJH

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.021			00.10	NONE
X	1	020.9	014.7	0.021			06.30	MOD
X	1	020.9	014.7	0.015			01.10	MOD
X	2	020.9	014.7	0.023			00.10	NONE
X	1	020.9	014.7	0.023			06.70	MOD
B	2	020.9	014.7	0.010			00.10	NONE
B	1	020.9	014.7	0.010		00.40	06.10	NONE
A	2	020.9	014.7	0.010			00.10	NONE
A	1	020.9	014.7	0.010			02.80	NONE
C	2	025.9	014.3	0.019			01.20	NONE
C	1	025.9	014.3	0.019		00.30	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	1.57	.09	.76	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63507 SHIM AL 50524H39 GID: CQFKXX

MANF: SPEC: MIL-S-22499C2T1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	S	SEE TEST REPORT

TOXICITY

69830 SHOCK ABSORBER M5205-TXE

MANF: BARRY CONTROLS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.22	.05	.00	

ODOR

RT	RT WEIGHT	CURE
	V 74.26	

TOXICITY

20677 SHOE HEEL MEGLITE GID: DOFDXX

MANF: GOODYEAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.500		00.11	03.50	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	A 00074.51	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006510 7

60912 SHOE POLISH KIWI BROWN GID: AKXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	A	00056.59	

20678 SHOE SOLE NEOPRENE 9 IRON GID: DOFDXX

MANF: SPACE CITY SHOE REP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.193		00.11	13.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	A	00201.66	

20667 SHOE SPRAY BLACK 317 GID: AKXXXX

MANF: MAGID CORP SPEC: ST44S1120-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003	00.00	00.00	NONE
A	1	033.0	014.3	0.001	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	X	00001.34	168H-70F- 24H-150F-

62211 SHOE TENNIS NYLON/RUBBER GID: FGBSHD

MANF: CONVERSE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.7			00.07	06.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	B	00518.66	72H-120F-

20519 SHROUD CUTTER P/N60C6037 GID: EXXXXX

MANF: GFE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.400		00.28	04.10	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	A	00044.35	

63861 SIEVE MOLECULAR GID: EXXXXX

MANF: UNION CARBIDE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	K	00083.95	

69995 SILICA CAB-O-SIL M-5

MANF: CABOT CORP

....NO TEST DATA AVAILABLE....

05954 SILICA DYNASIL 5000 FUSED INORGANIC

MANF: DYNASIL CORP SPEC: MIL-174C1GRB

FLAMMABILITY

RT	TEST	[illegible]	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	[illegible]	014.7	0.025		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006511 9

05954 SILICA DYNASIL 5000 FUSED INORGANIC (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.7	0.025		00.00	00.00	NONE
A	1	024.5	014.7	0.025		00.00	00.00	NONE
A	1	025.9	014.7	0.025		00.00	00.00	NONE
A	1	030.0	014.7	0.025		00.00	00.00	NONE
A	1	100.0	014.7	0.025		00.00	00.00	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.16	.06	.05	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00043.37	

20071 SILICA FUSED INORGANIC GID: DOHOHO

MANF: AQM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025		00.00	00.00	NONE
A	1	023.8	014.7	0.025		00.00	00.00	NONE
A	1	024.5	014.7	0.025		00.00	00.00	NONE
A	1	025.9	014.7	0.025		00.00	00.00	NONE
A	1	030.0	014.7	0.025		00.00	00.00	NONE
A	1	100.0	014.7	0.025		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.16	.06	.05	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00043.37	

05652 SILICA FUSED SLIPCAST INORG GID: DOHOHO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.038			01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.2E-6	.96	.02	.05	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

65038 SILICON CARBIDE DISCONT ON AL GID: DKXXXX

MANF: ROCKWELL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	275	72	-297	0.100	0	40

65037 SILICON CARBIDE ON AL 6061 GID: DKXXXX

MANF: ROCKWELL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	275	72	-297	0.060	0	40

85505 SILICONE RUBBER, TR9904

MANF: KIRKHILL RUBBER SPEC: STR5-2738

....NO TEST DATA AVAILABLE....

65061 SINGLE LAYER TAPE/BENDIX CLAMP GID: EXXXXX

MANF: BENDIX SPEC: NLS6E16-XX
MOXNESS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3				00.25	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006512 0

20324 SLEEVING DACRON WOVEN FABRIC GID: BFCBXX
MANF: FABRIC DEVELOPMENT SPEC: ST18T070-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.008		00.14	12.00	T MOD
X	1	025.9	014.3	0.008		00.42	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	.59	.23		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
V	00009.36	

85431 SLEEVING EXPANDO 686 TIGHTWEAVE POLYPHENYLENE SULFIDE
MANF: BENTLEY HARRIS SPEC: P/N 6753067-29

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.022		00.11	03.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	21.4	

20618 SLEEVING NOMEX BRAID GID: EFBVXX
MANF: TITEFLEX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0				01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85500 SLEEVING PVC POLYMER P/N 96M87264-1
MANF: B C INSULATION SPEC: MIL-I-3190 CL B
....NO TEST DATA AVAILABLE....

61367 SLIPPER SOCKS GID: FGBVGZ
MANF: EASTERN MTN SPORTS SPEC: ST10F1369-01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00152.46	

69970 SOAP DISH TRAVEL
MANF: DURAY INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	032.0	010.0	1.500		0.1	12.60	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	67.795	

20680 SOAP IVORY 2OZ GID: DDELXX
MANF: IVORY SPEC: HSB-2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	1.500		00.11	03.70	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00080.22	

80028 SOAP NON-FOAMING GID: EXXXXX
MANF: NASA SPEC: SED48101653-501

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
V	20.044	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006513 2

63206 SOCKET NYLON/GLASS FILL GID: DDBSIA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.145		00.03	02.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62121 SOCKS COTTON TUBE GID: BFFSXX

MANF: INTERWOVEN INC

SPEC: ST11C802

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00041.11	

63508 SOCKS PATAGONIA GID: BFXXXX

MANF: PATAGONIA

SPEC: PILE 29200

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.032		00.14	12.00	T LARGE
X	2	025.9	014.3	0.026		00.06	12.50	LARGE
X	1	025.9	014.3	0.026		00.30	12.70	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00062.20	

20559 SOCKS TUBE 90% COTTON 10%NYLON GID: BFFSBS

MANF: INTERWOVEN INC

SPEC: ST11C802-01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00035.95	

05661 SODIUM SILICATE(N) INORGANIC

MANF: PHILADELPHIA QUARTZ

....NO TEST DATA AVAILABLE....

80031 SOLDER KESTER SN 96 GID: FKXXXX

MANF: KESTER SOLDER

SPEC: QQ-S-571WS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	1000	72	75	0.031	00	10
I	MECH	4000	72	75	0.031	00	10
B	MECH	6000	72	75	0.031	00	20

64245 SOLDER SLEEVE D101-00

MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.030			03.90	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00022.05	

69890 SOLIDOX TYPE "B" IGNITER

MANF: COOPER GROUP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
S								NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64110 SOLUTION 12% STERICIDE GID: BVFCXX

MANF: PENNWALT CORP

SPEC: ST80S589-01

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006514 4

64110 SOLUTION 12% STERICIDE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	X	00000.07	36H-70F-

06195 SOUND INSUL KNB-5LR BLACK PVC GID: FJAEXX

MANF: KINETICS INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.033			00.30	NONE
C	1	023.8	014.5	0.033		00.24	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	V	00020.38	

63975 SOUND INSUL KNM-50B GID: FJXXXX

MANF: PEABODY NOISE CONTROL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.060		00.03	12.00	T MOD
X	1	030.0	010.0	0.060		00.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	A	21.895	

63207 SOUNDSCREEN FOAM/METAL/FOAM GID: CCGICQ

MANF: ALLFORCE ACOUSTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	1.275		00.60	08.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61172 SPATULA RUBBERMAID 1904 GID: EXCYXX

MANF: RUBBERMAID

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	K	00018.90	

20774 SPHERES FILTER EPOXY UMPQUA

....NO TEST DATA AVAILABLE....

61072 SPLICES NYLON STA-KON GID: BCBSXX

MANF: THOMAS & BETTS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.32	.06	.00	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

60652 SPONGE ESTER POLYURETHANE GID: CACQXX

MANF: CLEAN ROOM PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	020.2	0.120		16.40	12.00	T MOD
X	1	100.0	020.2	0.120		12.00	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	[illegible]	00019.[illegible]	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006515 6

60698 SPONGE FLUOREL RL 4714 GID: ESDEXX
MANF: RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.058			02.40	SMALL
A	1	031.0	010.0	0.058			00.90	SMALL
A	1	043.2	008.0	0.060			02.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00010.70	

02882 SPONGE FLUOREL RL2060
MANF: RAYBESTOS-MANHATTAN SPEC: MB0130-084T2
....NO TEST DATA AVAILABLE....

60875 SPONGE FLUOROELASTOMER R1M693 GID: ESDEXX
MANF: RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.082			02.90	NONE
B	1	031.0	010.0	0.081		00.15	08.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00010.25	

63406 SPONGE MOSITE GID: DOXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
S		020.9		0.312				NONE
S		030.0		0.562				NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06429 SPONGE RUBBER CELLULOSE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	24.50	.43	2.50	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

62113 SPONGE RUBBER ENSOLITE AL PVC/NITRILE GID: CAHCXX
MANF: EXPANDED RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.750			00.20	NONE
C	1	025.9	014.3	0.750			12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
V	00020.36	

20323 SPONGE RUBBER LATEX KOYLON GID: CAACXX
MANF: HARRY GOLDMAN FOAM SPEC: ST67L073-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.221		00.18	12.00 T	MOD
X	1	025.9	014.3	0.221		00.73	12.00 T	NONE
X	2	025.9	014.3	0.700		00.17	12.00 T	MOD
X	1	025.9	014.3	0.700		01.89	11.70 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	2.62	1.04		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
V	00008.36	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006516 8

05436 SPONGE RUBBER NEOPRENE GID: DODBXX

MANF: DUPONT SPEC: ASTM D1056-68

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	019.0	014.3	0.250			02.00	NONE
X	1	025.9	014.3	0.150		00.90	12.00	T MOD
I	1	030.0	008.0	0.245		00.26	12.00	T NONE
I	1	040.0	008.0	0.245		01.09	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.40	

20042 SPONGE RUBBER NEOPRENE GID: DODBXX

MANF: ELMHURST RUBBER CO
KIRKHILL RUBBER SPEC: MIL-R-6130T1GRA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.500			00.70	NONE
A	1	030.0	009.0	0.475			02.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.7E-7	9.43	4.20		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00058.48	

61623 SPONGE RUBBER NEOPRENE CLOSED CELL KNIT GID: CEDBXX

MANF: KIRKHILL RUBBER SPEC: ST61N1598-07

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.100		00.90	12.00	T NONE
I	1	025.9	014.3	0.190		00.60	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.12	.03	.00	16H-399F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05524 SPONGE RUBBER NEOPRENE KOYLON GID: CADBXX

MANF: UNIROYAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.500			00.80	NONE
A	1	025.9	014.3	1.100			01.00	NONE
A	1	025.9	014.3	1.000			01.90	NONE
A	1	030.0	010.4	1.000			02.00	NONE
A	1	030.0	010.4	1.100			01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.7E-6	1.75	.71		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.63	

20647 SPONGE RUBBER NEOPRENE OPEN CELL 2-S-198 GID: CCDBXX

MANF: KIRKHILL RUBBER SPEC: AMS 3198

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.250			00.10	NONE
C	1	025.9	014.3	0.250		00.12	11.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.4E-6	8.98	1.33		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00009.99	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006517 T

61865 SPONGE RUBBER NEOPRENE R422M GID: CCDBXX

MANF: RUBATEX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	1.200			01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61003 SPONGE RUBBER NEOPRENE R425M GID: CHDBXX

MANF: RUBATEX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.250		00.13	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00017.63	

61871 SPONGE RUBBER NEOPRENE STY36-2V 40LB GID: ESDBXX

MANF: REPUBLIC RUBBER PROD SPEC: ST67N159

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.231			00.10	NONE
C	1	023.8	014.5	0.231		00.12	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.8E-6	17.05	8.81		60H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	A	00025.70	

02921 SPONGE RUBBER SILICONE GID: DOCKXX

MANF: ABLE INDUS
BOYD INDUS RUBBER
CONN HARD RUBBER
GROENDYK
KIRKHILL RUBBER

SPEC: AMS 3195

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.190			01.70	NONE
B	2	020.9	014.7	0.143			00.10	NONE
B	1	020.9	014.7	0.143		00.03	09.00	NONE
C	2	023.8	014.5	0.190			00.10	NONE
C	1	023.8	014.5	0.190		00.07	12.00	T NONE
C	2	023.8	014.5	0.049			01.40	NONE
C	1	023.8	014.5	0.049		00.14	12.00	T SMALL
A	1	023.8	014.5	0.515			00.20	NONE
X	2	025.9	014.3	0.190			00.20	NONE
X	1	025.9	014.3	0.190		00.07	12.00	T MOD
C	2	025.9	014.3	0.250			01.20	NONE
C	1	025.9	014.3	0.250		00.10	12.00	T NONE
C	2	030.0	010.0	0.125		00.09	04.63	NONE
C	1	030.0	010.0	0.125		00.10	12.00	T NONE
B	2	030.0	010.0	0.197		00.02	00.10	NONE
B	1	030.0	010.0	0.197		00.03	07.00	NONE
I	2	100.0	019.0			01.32	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.6E-7	.11	.01		16H-480F-

ODOR

RT	RT	WEIGHT	CURE
A	X	00020.03	

02952 SPONGE RUBBER SILICONE GID: CACKXX

MANF: CONN HARD RUBBER SPEC: AMS 3196 ST67F636-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	010.0	0.132		00.10	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006518 1

02952 SPONGE RUBBER SILICONE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.187			02.80	NONE
C	1	025.9	014.3	0.187		00.05	12.00	T NONE
C	1	030.0	010.0	0.130		00.06	12.00	T NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.12	.43	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.19	

05143 SPONGE RUBBER SILICONE GID: DOCKXX

MANF: AUBURN MFG SPEC: AMS 3327

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.131		00.09	12.00	T SMALL
C	2	030.0	010.0	0.069			00.10	NONE
C	1	030.0	010.0	0.069		00.09	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	1.20	.26		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.21	

05211 SPONGE RUBBER SILICONE GID: CACKXX

MANF: GROENDYK SPEC: AMS 3196

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.062			00.10	NONE
C	1	023.8	014.5	0.062		00.13	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.11	.03	.00	24H-360F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00012.60	

05026 SPONGE RUBBER SILICONE 14143 GID: DOCKXX

MANF: MOSITES RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.60	.35	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00017.74	

06031 SPONGE RUBBER SILICONE ADHESIVE PS GID: DOCKXX

MANF: SPEC: MB0130-150

....NO TEST DATA AVAILABLE....

06612 SPONGE RUBBER SILICONE F760 GID: CHCKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.320			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62423 SPONGE RUBBER SILICONE FOMEGA HT603 GID: CACKXX

MANF: BISCO PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	1.000			00.70	NONE
A	1	025.9	014.3	0.240			01.30	NONE
A	1	030.0	010.0	1.000			00.30	NONE
A	1	030.0	010.0	0.240			01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.12	.49		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00023.10	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006519 3

65461 SPONGE RUBBER SILICONE KE901FU
MANF: SHIN-ETSU CHEMICAL

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	024.5	014.5	0.120			00.20	NONE	No test data	No test data							
C	1	024.5	014.5	0.120		00.10	12.00	T NONE									

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data							X 00021.66	

63099 SPONGE RUBBER SILICONE PD200 GID: CACKXX

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.310			02.50	NONE	No test data	No test data							
I	1	020.9	014.7	0.250		00.03	12.00	T NONE									

63056 SPONGE RUBBER SILICONE PD200-16 GID: CCDPXX
MANF: GENERAL ELECTRIC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.111	0.064	00.00	00.00	NONE	No test data	No test data							
I	1	030.0	014.7	0.111	0.064	00.10	10.00	T NONE									

05011 SPONGE RUBBER SILICONE PD200-16 SILICONE GID: CACKXX
MANF: GENERAL ELECTRIC SPEC: MB0130-099

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.08	.00	.00	10H-199F- 10H-300F- .5H-649F- 48H-351F-0psiaVACUUM		X 00008.18	48H-250F-0psiaVACUUM

64971 SPONGE RUBBER SILICONE PD200-16/RTV560 GID: CCDPXX
MANF: GENERAL ELECTRIC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.106	0.064	00.00	00.00	NONE	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	1.0E-6	.03	.02	.00	10H-199F- 10H-351F- 24H-351F-0psiaVACUUM	No test data		

63061 SPONGE RUBBER SILICONE PD200-16/RTV560/PD147 GID: CCCKXX
MANF: GENERAL ELECTRIC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.125	0.090	00.00	00.00	NONE	No test data	No test data							
A	1	025.0	014.5	0.125	0.090		00.50	NONE									
A	1	030.0	014.5	0.125	0.090		01.00	NONE									

61335 SPONGE RUBBER SILICONE PR855 FR GID: CACKXX
MANF: CHASE TECHNOLOGY
PROD RESEARCH & CHEM

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.500			00.50	NONE	No test data	No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006520 T

61335 SPONGE RUBBER SILICONE PR855 FR (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.500			00.30	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.6E-6	1.83	.40	.02	

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

TOXICITY

RT	RT	WEIGHT	CURE
A	X	00020.29	24H-70F-

61363 SPONGE RUBBER SILICONE PR855-2 FR GID: DPCKXX

MANF: CHASE TECHNOLOGY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.800			00.40	NONE
A	1	030.0	009.0	0.880			00.30	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.88	.44	.00	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

TOXICITY

RT	RT	WEIGHT	CURE
	X	00020.25	24H-70F-

80025 SPONGE RUBBER SILICONE RT 762 FR GID: CACKXX

MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.153			03.70	NONE
A	1	030.0	010.0	0.154			05.30	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	1.36	.40	.02	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

TOXICITY

RT	RT	WEIGHT	CURE
	A	21.604	

05885 SPONGE RUBBER SILICONE Y3233 GID: DOCKXX

....NO TEST DATA AVAILABLE....

05691 SPONGE RUBBER VITON 1028

MANF: MOSITES RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.116			00.10	NONE
A	1	023.8	014.5	0.230			05.20	SMALL
A	1	025.8	014.3	0.220			01.80	NONE
A	1	030.0	009.0	0.131			01.30	SMALL
A	1	033.2	015.5	0.220			02.00	SMALL
A	1	035.0	014.3	0.220			02.80	SMALL
A	1	040.0	014.3	0.220			02.10	SMALL
X	1	045.0	014.3	0.220		00.12	12.00	T MOD
X	1	050.0	014.3	0.220		00.05	10.00	MOD
X	2	100.0	020.2	0.131		00.27	12.00	T MOD
X	1	100.0	020.2	0.131		00.98	12.00	T MOD
X	1	100.0	005.0	0.230		00.17	12.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.30	.08	.00	96H-257F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

TOXICITY

RT	RT	WEIGHT	CURE
A	A	00020.04	

20611 STAIN TRANSPARENT GID: AKXXXX

MANF: DYKEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.100			00.80	NONE
A	1	030.0	014.3	0.100			01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006521 1

20611 STAIN TRANSPARENT (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.2E-7	.19	.02		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

63743 STORAGE CAN FOR RECORDING TAPE GID: EXXXXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	01431.30	

69896 STRAP CARBON GRAPHITE IM-6 EPOXY

MANF: STRUCTURAL COMPOSITES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.103		00.05	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	34.60	

20450 STRAP ELASTIC FSM 8305

....NO TEST DATA AVAILABLE....

61459 STRAP ELEC AL KAPTON/PBI GID: FJFJCD

MANF: NATIONAL METALLIZING
SHELDAHL

SPEC: MD411-4010

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.026			05.70	NONE
A	1	020.9	014.7	0.095			01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60905 STRAP EYEGLASS RETENTION GID: BFXXXX

MANF: CROAKIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.34	

69897 STRAP GLASS S2/EPOXY

MANF: STRUCTURAL COMPOSITES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.077		0.07	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	X 7.629	

61806 STRAP GROUNDING TCS NOMEX/KAPTON GID: BNCDBV

MANF: ROCKWELL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.027			03.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61611 STRAP NEOPRENE/COTTON/RUBBER GID: BFHDFS

MANF: ALLIANCE WEBBING INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.125		00.39	10.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006522 3

61611 STRAP NEOPRENE/COTTON/RUBBER (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00014.84	

63209 STREAMER WARNING COTTON GID: BFFSXX

MANF: ELIZABETH WEBBING CO SPEC: NAS1089-24

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.030		01.00	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05835 STREAMER WARNING MD175-6108

....NO TEST DATA AVAILABLE....

62476 SUCTION CUP RUBBER STILSON4037 GID: DDHDXX

MANF: STILSON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5			00.04	06.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00223.07	

20683 SUNGLASSES AND CASE GID: EXXXXX

MANF: AMERICAN OPTICAL SPEC: DSA 12074C1103 MIL-S-25948

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00086.46	

20734 SWAB DISPOSABLE

....NO TEST DATA AVAILABLE....

62406 SYRINGE 60 CC POLYPROPYLENE/SILICONE GID: FCXXXX

MANF: BURRON MEDICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00041.34	

20622 TAMPONS DEODORANT SUPER PLUS GID: DDXXXX

MANF: PLAYTEX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00021.23	

85367 TAPE 003004SX1014 COLOR 4 ANODIZED ALUMINUM WITH PS ACRYLIC ADHESIVE

MANF: SEOLOC SCREENING INC SPEC: STM0599-09

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.005	0.034		00.12	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.0E-6	.46	.07	.06	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00005.71	

61085 TAPE 2345-1 KAPTON/SILICONE GID: DZCDCK

MANF: DODGE SPEC: MB0135-050 MB0135-050T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006523 5

61085 TAPE 2345-1 KAPTON/SILICONE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.1E-7	.73	.25		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

85397 TAPE 322 AL FOIL/ADHESIVE

MANF: NASHUA CORP

....NO TEST DATA AVAILABLE....

60699 TAPE 58 GID: DYXXXX

MANF: TUCK INDUSTRIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.61	.32	.00	SEE TEST REPORT

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	00010.64	

63240 TAPE 6083 TFE/GLASS GID: DYCNXX

MANF: TACONIC PLASTIC LTD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.010			08.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60395 TAPE 898

MANF: SPEC: USBI99605-0015

....NO TEST DATA AVAILABLE....

65165 TAPE 925 ALUMINUM WITH POLYESTER ADHESIVE GID: DYFKCB

MANF: NEW ENGLAND TAPE CO SPEC: MIL-I-631TGFF MMS-J-690A

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.28	.04	.06	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

60494 TAPE ACETATE/LEXAN TP1-31 GID: DYCBCA

MANF: BISHOP GRAPHICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.062			01.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT WEIGHT	CURE
V	00012.02	

64099 TAPE ADHESIVE SILICONE GLASS/REINFORCED GID: ZCKIAM

MANF: MOXNESS SPEC: MIL-I-22444

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.9E-6	1.06	.24	.03	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

63993 TAPE AL/KAPTON/DACRON/CHEMGLAZE 202 GID: BFCDXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.009		02.26	08.40	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06432 TAPE AL/KAPTON/ORGANIC COATED GID: DYCDFJ

MANF: SHELDAHL SPEC: MB0135-083

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.009			00.10	NONE
C	1	020.9	014.7	0.009		00.83	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006524 7

06432 TAPE AL/KAPTON/ORGANIC COATED (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	1.18	.00	.91	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

63509 TAPE ALL WEATHER CW3 GID: DYXXXX

MANF: MANCO INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	K	00019.63	

63221 TAPE ALUMINIZED KAPTON 14162-51 GID: DZFJXX

MANF: NATIONAL METALLIZING SPEC: STM 0695-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.004			05.50	NONE
C	1	024.5	014.5	0.004		00.51	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.6E-6	.91	.30	.13	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	A	00008.94	

61440 TAPE ALUMINUM FOIL M90006 ADHESIVE GID: DYXXXX

....NO TEST DATA AVAILABLE....

69796 TAPE ALUMINUM FOIL/GLASS CLOTH 2922-7

MANF: OAK INDUSTRIES

....NO TEST DATA AVAILABLE....

85383 TAPE ANODIZED ALUMINUM/ACRYLIC PRESSURE SENSITIVE GID: DYXXXX

MANF: SEOLOC SCREENING INC

....NO TEST DATA AVAILABLE....

65030 TAPE ANTI-SLIP SAFETY SEE TEST REPORT GID: DYXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
S	HYZE
S	MMH
S	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85499 TAPE AR559 WITH SILICONE TRANSFER ADHESIVE

MANF: ADHESIVE RESEARCH CORP

....NO TEST DATA AVAILABLE....

61730 TAPE ARMAFLEX LA3500 10-67 PS GID: DZDJCU

MANF: ARMSTRONG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.150			02.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	V	00015.91	

60326 TAPE BLASTAPE 2 STYLE MX4703

MANF: JOHNS-MANVILLE SPEC: STW4-2563

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006525 9

80201 TAPE BUNDLING GLASS FABRIC GID: DYXXXX
MANF: GUDEBROD BROS SILK SPEC: MIL-T-43435B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.460			01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	22.480	

65443 TAPE C666 GID: DZXXXX
MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.005	0.003		02.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00021.87	

60677 TAPE CASSETTE GID: FCXXXX
MANF: PAYTEL SYSTEMS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	01259.58	

62174 TAPE CASSETTE 10635183 D3 GID: FCXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.320			01.40	NONE
I	1	033.0	014.3	0.320		00.01	04.10	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00043.41	

61350 TAPE CASSETTE MC60 GID: FCXXXX
MANF: OLYMPUS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00027.12	

61227 TAPE CASSETTE MEMOREX 120 GID: EXXXXX
MANF: MEMOREX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	38.95	

61064 TAPE CHARTPAK GRAPHIC 5003 BLUE GID: DIXXXX
MANF: TIMES MIRROR CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	025.9	014.3	0.015		00.09	08.00	T SMALL
I	2	030.0	010.4	0.015		00.13	08.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.81	

62378 TAPE CHARTPAK GRAPHIC 5005 ORANGE GID: DZXXXX
MANF: TIMES MIRROR CO

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006526 0

62378 TAPE CHARTPAK GRAPHIC 5005 ORANGE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	025.9	014.3	0.015		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.62	

61011 TAPE CHARTPAK GRAPHIC 5014 PS BROWN GID: DZXXXX

MANF: TIMES MIRROR CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	025.9	014.3	0.014		00.09	08.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00018.00	

62358 TAPE CHARTPAK GRAPHIC 5017 GREEN GID: DYXXXX

MANF: TIMES MIRROR CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	025.9	014.3	0.015		00.10	08.00	T NONE
I	2	030.0	014.3	0.015		00.13	08.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00010.06	

80295 TAPE CHOFOIL 101 COPPER FOIL GID: DYXXXX

MANF: CHOMERICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.8	014.3	0.008		0.26	07.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20663 TAPE CORRECT 7510-00-634-5110 GID: DZGMXX

MANF: GFE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.2E-6	9.99	4.24		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00013.36	

20772 TAPE CORRECTION

....NO TEST DATA AVAILABLE....

60159 TAPE COTTON ALL TYPES GID: DYXXXX

MANF: SPEC: MIL-T-5661

....NO TEST DATA AVAILABLE....

05255 TAPE DACRON GID: DYXXXX

....NO TEST DATA AVAILABLE....

64140 TAPE DISSOLVO WELDING ADHESIVE

MANF: GILBERT INTERNATIONAL

....NO TEST DATA AVAILABLE....

85487 TAPE DL279 SILICONE

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	24.5	14.5	.007	.003		5.0	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006527 2

85487 TAPE DL279 SILICONE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	25.9	14.3	.007	.003		5.75	NONE
B	1	30.0	10.2	.007	.003		7.25	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

63715 TAPE DOUBLE STICKY BACK DVF1 GID: DZXXXX

MANF: MANCO INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00009.70	

20769 TAPE DUCT CLOTH ST260 GID: DYXXXX

MANF: SPECTAPE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.014	0.003	00.40	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.4E-5	3.20	1.39		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.44	

06633 TAPE DW204 TFE/SILICONE GID: DZCKCN

MANF: DE WAL IND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.006	0.003		02.20	NONE
A	1	030.0	010.0	0.006	0.003		02.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.3E-6	.65	.33	.04	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.88	

05931 TAPE E125 TEFLON GID: DYCNXX

MANF: DODGE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002			03.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00005.62	

62267 TAPE EDGING 750 ACETATE PAPER WITH ADHESIVE GID: DZFUXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.005	0.010	00.00	00.00	NONE
B	1	025.9	014.3	0.005	0.010		06.50	NONE
A	1	030.0	009.0	0.005	0.010		05.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00020.36	

20431 TAPE ELASTIC .75 WIDE GID: EABVXX

MANF: SMITH
STYLASTIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.030		00.70	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006528 4

20431 TAPE ELASTIC .75 WIDE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00019.98	

TOXICITY

61608 TAPE ELASTIC 14738P/B8209W GID: EAXXXX

MANF: WYOMISSING CORP SPEC: ST13W702

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.045		00.05	12.00	T NONE
C	1	025.9	014.3	0.045		00.58	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-6	2.93	.26		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.40	

TOXICITY

61965 TAPE ELASTIC RUBBER GID: DXHDXX

MANF: SCOVILL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.034		00.89	01.20	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00013.52	

TOXICITY

63222 TAPE ELECTRIC POLYESTER TYPE GFT PS ADHESIVE GID: EBCBXX

MANF: . SPEC: MIL-I-15126TGFT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.3	0.008		00.41	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20741 TAPE FABRIC C516 VINYL COATED GID: DZCKXX

MANF: ARNO PRODUCTS SPEC: ST13D1162-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.700			01.20	NONE
A	1	025.9	014.3	0.011	0.003		02.60	SMALL
A	1	030.0	009.0	0.015	0.003		03.30	SMALL
A	1	030.0	010.4	0.012	0.003		01.70	SMALL
A	2	033.0	014.3	0.013	0.003		00.10	NONE
A	1	033.0	014.3	0.013	0.003		06.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	8.2E-7	3.72	1.63		24H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	V	00020.71	

TOXICITY

63741 TAPE FASTAPE A PS GID: EXXXXX

MANF: FASSON SPEC: ST13T1931-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.010		00.00	00.00	NONE
C	1	030.0	010.0	0.010		00.20	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00018.82	

TOXICITY

06318 TAPE FES51 ALUMINUM GLASS WITH SILICONE ADHESIVE GID: DZCKFJ

MANF: TUCK INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.008	0.003		04.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006529 6

06318 TAPE FES51 ALUMINUM GLASS WITH SILICONE ADHESIVE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.008	0.003		03.90	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.26	.67	.00	

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	K 00019.58	

61260 TAPE FGA32600 ALUMINIZED GID: DZFJXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003	0.003		02.30	NONE
I	.1	025.9	014.3	0.003		01.50	06.00 T	NONE
I	1	025.9	014.3	0.005		00.50	12.00 T	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	.69	.15		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	1.5	

20112 TAPE FIBERGLASS COATED WITH PYRE ML GID: DYGDXX

....NO TEST DATA AVAILABLE....

65382 TAPE FIBERGLASS QUIK-TAPE GID: DXXXXX

MANF: QUICK-TAPE SALES CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.010	0.003		04.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65214 TAPE FLEXITE TGL BLUE ADHESIVE GID: DYXXXX

MANF: MARKEL CORP

SPEC: LFM 46187

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.26	.36	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

64257 TAPE FLUORGLAS 2346-1 ADHESIVE GID: DYBPJA

MANF: OAK INDUSTRIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.8E-6	.39	.10	.17	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

63223 TAPE FLUORGLAS 2915 PS ADHESIVE GID: DZGDXX

MANF: DODGE

SPEC: MIL-I-19166

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.008			05.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61576 TAPE FLUORGLAS ALUMINUM/GLASS SILICONE ADHESIVE GID: DZIAFJ

MANF: DODGE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.004		00.00	00.00	NONE
C	1	020.9	014.7	0.004		02.93	12.00 T	NONE
I	1	030.0	009.0	0.004		02.61	12.00 T	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	5.0E-6	2.11	.86	.02	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006530 2

61587 TAPE FLUORGLAS/TEFLON GID: DYCNXX
MANF: DODGE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.3E-6	.38	.12	.05	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20478 TAPE FR357 ADHESIVE WITH BACKING GID: DZFSXX
MANF: NASHUA CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.013	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.013	0.003	00.20	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	X 00026.41	

TOXICITY

64044 TAPE G103760 FEP/ARAMID GID: DYBOXX
MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.010	01	02

05569 TAPE G143902 TFE/GLASS/GOLD/SILICONE ADHESIVE GID: DZCNIA
MANF: SHELDAHL SPEC: MB0135-059 MB0135-059T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		02.20	NONE
A	1	025.9	014.3	0.005	0.003		01.30	SMALL
A	1	030.0	009.0	0.005	0.003		01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	.60	.29	.05	

ODOR

RT	RT WEIGHT	CURE
A	00012.96	

TOXICITY

85457 TAPE G148000 VACUUM DEPOSITED ALUMINUM X 0.5 MIL KAPTON X 3P ADHESIVE X 0.9 OUNCE GID: DYXXXX
MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.007		00.27	7.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06279 TAPE G148020 AL/POLY/NOMEX/ADHESIVE GID: FJCDBV
MANF: SHELDAHL SPEC: MB0135-079 3 MB0135-079T1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.1E-6	1.26	.01		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64043 TAPE G400200 2.0 MIL TYPE A TEFLON WITH VAC DEPOSITED ALUMINUM WITH 966 ACRYLIC ADHESIVE GID: DYBOXX
MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	15	-297	0.005	0	20

64899 TAPE G400300 2 MIL TYPE A TEFLON WITH VACUUM DEPOSITED SILVER AND INCONEL
MANF: SHELDAHL
....NO TEST DATA AVAILABLE....

64894 TAPE G400600 .5 MIL TYPE A TEFLON WITH VAC DEPOSIT SILVER WITH VAC DEPOSITED INCONEL WITH 966 ACRYLIC ADHESIV GID: DYXXXX
MANF: SHELDAHL
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006531 4

65439 TAPE G401000 VACUUM DEPOSITED ALUMINUM 1 MIL KAPTON WITH 966 ACRYLIC ADHESIVE GID: DYCDAK

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.5			00.07	07.50	NONE
B	1	024.5	014.5			00.08	08.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.76	.01	.33	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
A	00007.39	

06141 TAPE G401900 5 MIL TYPE A TEFLON WITH VAC DEPOSITED SILVER AND INCONEL WITH 966 ACRYLIC ADHESIVE GID: DZXXXX

MANF: SHELDAHL SPEC: MB0135-063T1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-7	.10	.00		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

05955 TAPE G401902 FEP WITH 467 ACRYLIC ADHESIVE GID: DYAKXX

MANF: SHELDAHL

....NO TEST DATA AVAILABLE....

61496 TAPE G402410 VACUUM DEPOSITED ALUMINUM 1 MIL KAPTON GID: DYXXXX

MANF: SHELDAHL

....NO TEST DATA AVAILABLE....

05240 TAPE G402600 VACUUM DEPOSITED GOLD 1 MIL KAPTON WITH MYSTIC 7361 SILICONE ADHESIVE GID: DYDPXX

MANF: SHELDAHL SPEC: MB0135-050T2

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.27	.10	.00	24H-150F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

05831 TAPE G404200/G404202TFE/AG/SILICONE ADHESIVE GID: DZCNCK

MANF: SHELDAHL SPEC: MB0135-063 MB0135-063T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005	0.003		01.40	NONE
A	1	030.0	010.0	0.006	0.003		01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.2E-6	.24	.11	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
V	00017.19	

05832 TAPE G404300/G404302 5 MIL TYPE A TEFLON WITH VACUUM DEPOSITED SILVER AND INCONEL WITH PERMACEL 223 SILICONE GID: DYCNCK

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7			00.10	02.75	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.2E-6	.69	.27		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

65438 TAPE G405110 1 MIL KAPTON WITH VACUUM DEPOSITED ALUMINUM GID: DYCDXX

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.5			00.00	00.00	NONE
A	1	020.9	014.5			00.16	03.00	NONE
B	1	024.5	009.0			00.28	08.75	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.68	.02	.60	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00016.10	

Information Handling Services, 2000

61561 TAPE G406400/G406402 VACUUM DEPOSITED GOLD AND 1 MIL KAPTON WITH ACRYLIC ADHESIVE GID: DYCDAK

MANF: SHELDAHL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.75	.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65525 TAPE G406510 1 MIL TEFLON WITH 966 ACRYLIC ADHESIVE GID: DYAKXX

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.001	0.003		03.60	NONE
A	1	023.8	014.3	0.001	0.003		03.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	1.05	.04	.31	

ODOR

RT	RT WEIGHT	CURE
A	00017.68	

TOXICITY

65457 TAPE G406520 2 MIL TEFLON WITH 966 ACRYLIC ADHESIVE GID: DYXXXX

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002			01.90	NONE
A	1	025.9	014.3	0.002			02.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-6	1.10	.06	.33	

ODOR

RT	RT WEIGHT	CURE
K	18.21	

TOXICITY

06436 TAPE G406550 5 MIL TEFLON WITH 966 ACRYLIC ADHESIVE GID: DYCOAK

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.007	0.003		02.40	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.20	.02	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06013 TAPE G40700 KAPTON/GOLD ADHESIVE GID: DYCDMU

SPEC: MB0135-061T11C2

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005			02.70	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.3E-6	.06	.00		24H-150F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61103 TAPE G407700 KAPTON VACUUM DEPOSITED ALUMINUM WITH SILICONE ADHESIVE GID: DYCDCK

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.004	0.003		01.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	7.6E-7	2.58	.83		24H-150F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20556 TAPE G407810 VACUUM DEPOSITED ALUMINUM 1 MIL KAPTON WITH 1 MIL SILICONE ADHESIVE GID: DYMACC

SPEC: STSV128 S4

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002	0.003		03.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20556 TAPE G407810 VACUUM DEPOSITED ALUMINUM 1 MIL KAPTON WITH 1 MIL SILICONE ADHESIVE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	2.58	.64	.34	

ODOR

RT	RT WEIGHT	CURE
A	A 00019.61	

TOXICITY

06481 TAPE G407910 VACUUM DEPOSITED GOLD 1 MIL KAPTON WITH SILICONE ADHESIVE GID: DYGFCD

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003	0.003		02.00	SMALL
A	1	025.9	014.3	0.003	0.003		01.70	SMALL
A	1	030.0	009.0	0.003	0.003		01.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.77	.03	.41	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60885 TAPE G407925 PS ADHESIVE GID: DZXXXX

MANF: SHELDAHL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	1.73	.38		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61080 TAPE G408100 INCONEL SILICONE ADHESIVE GID: DZCKMN

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.007	0.003		01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.6E-7	.86	.28		

ODOR

RT	RT WEIGHT	CURE
	A 00020.70	

TOXICITY

65437 TAPE G408150 5 MIL TEFLON VACUUM DEPOSITED SILVER AND INCONEL WITH 1 MIL SILICONE ADHESIVE GID: DYXXXX

MANF: SHELDAHL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.20	.06	.01	

ODOR

RT	RT WEIGHT	CURE
	K 00027.81	

TOXICITY

60372 TAPE G408460 THICK BLACK FILM WITH .5 MIL KAPTON AND 1 MIL SILICONE ADHESIVE GID: DYXXXX

MANF: SHELDAHL

....NO TEST DATA AVAILABLE....

60371 TAPE G408862 ALUMINUM/KAPTON/ADHESIVE GID: DZFKXX

MANF: SHELDAHL

....NO TEST DATA AVAILABLE....

06280 TAPE G409360 THICK BLACK FILM WITH .5 MIL KAPTON AND 966 ACRYLIC ADHESIVE GID: DYXXXV

MANF: SHELDAHL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.94	.05	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06449 TAPE G411520 2 MIL RÍ KAPTON VACUUM DEPOSITED ALUMINUM WITH ACRYLIC OVERCOAT GID: DYCDFJ

MANF: SHELDAHL SPEC: MB0135-084T1C2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002			02.00	NONE
C	2	020.9	014.7	0.001			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006534 T

06449 TAPE G411520 2 MILSRÍ KAPTON VACUUM DEPOSITED ALUMINUM WITH ACRYLIC OVERCOAT (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	020.9	014.7	0.001		03.80	12.00 T	SMALL
B	2	025.9	014.3	0.002			00.20	NONE
B	1	025.9	014.3	0.002		00.29	10.30	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.86	.00	.79	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64493 TAPE G411600 AL-KAPTON/ORGANIC COATED GID: DYCDHS

MANF: SHELDAHL SPEC: MB0135-083

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.008			04.06	NONE
C	2	030.0	010.0	0.007		1.1	01.10	NONE
C	1	030.0	010.0	0.007		5.5	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	1.10	.02	.87	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05078 TAPE G411660 5 MIL KAPTON WITH VACUUM DEPOSITED ALUMINUM GID: DYXXXX

MANF: SHELDAHL SPEC: MB0135-048T2 MB0135-048T3

....NO TEST DATA AVAILABLE....

06504 TAPE G411970 ALUMINUM/KAPTON/ADHESIVE GID: DVCDFJ

MANF: SHELDAHL SPEC: MB0135-084C1T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.001			00.20	NONE
X	1	020.9	014.7	0.001		01.80	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.80	.05	.53	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64042 TAPE G412400 FEP/POLYIMIDE/ARAMID GID: DYBOXX

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.011	2	5

06011 TAPE G550 FIBERGLASS/ACRYLIC GID: DZFVAK

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.007	0.003		02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.30	.00	.00	

ODOR

RT	RT WEIGHT	CURE
A	K 00019.34	

TOXICITY

05597 TAPE GLASS A2278 ADHESIVE GID: DZGDXX

....NO TEST DATA AVAILABLE....

62348 TAPE GLASS/SILICONE/ADHESIVE PE2347 GID: DYCKIA

MANF: KEENE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.006			00.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006535 1

62348 TAPE GLASS/SILICONE/ADHESIVE PE2347 (cont)

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.006		00.60	12.00	T MOD										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.51	.20	.00	1H-347F-

ODOR			TOXICITY
RT	RT	WEIGHT	CURE
	V	00020.71	

60376 TAPE GLASS/THERMOSET PS GID: DYXXXX
MANF: AQM SPEC: MIL-T-4053
....NO TEST DATA AVAILABLE....

06187 TAPE GV FIBERGLASS/SILICONE/ADHESIVE GID: DZIACK

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.13	.58	.00	

ODOR			TOXICITY
RT	RT	WEIGHT	CURE
No test data			

63218 TAPE HI-TEMP ACRYLIC ADHESIVE GID: DYAKXX
MANF: 3M CO

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	024.5	014.5			00.75	12.00	T NONE	No test data		No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR			TOXICITY
RT	RT	WEIGHT	CURE
	A	00007.70	

06440 TAPE HI/D 603A KAPTON/ACRYLIC
MANF: TECHNICAL FLUOROCARBON

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.62	.13	.00	

ODOR			TOXICITY
RT	RT	WEIGHT	CURE
No test data			

05305 TAPE INSUL PJS C100-21 GID: DYXXXX
....NO TEST DATA AVAILABLE....

85496 TAPE J677 VINYL CLOTH WITH SILICONE ADHESIVE
MANF: W H BRADY
....NO TEST DATA AVAILABLE....

60401 TAPE JACKET 602-35-7010
....NO TEST DATA AVAILABLE....

20885 TAPE KAPTON AL/AU WITH Y966 ADHESIVE
MANF: SPEC: MB0125-067T1&2
....NO TEST DATA AVAILABLE....

63769 TAPE KAPTON AND TAPE HOLDER
MANF: DUPONT

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR			TOXICITY
RT	RT	WEIGHT	CURE
	A	00274.40	

61732 TAPE KAPTON K107 GOLD REINFORCED GID: DYMUCD
MANF: CONN HARD RUBBER

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.21	.49	.00	24H-150F-

ODOR			TOXICITY
RT	RT	WEIGHT	CURE
No test data			

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006536 3

05292 TAPE KAPTON/ACRYLIC ADHESIVE 2342-1R GID: DZCDAK

MANF: DODGE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.003	0.003		01.60	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.94	.44	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00005.24	24H-150F-

20162 TAPE KAPTON/ACRYLIC K109 GID: DZCDAA

MANF: CONN HARD RUBBER

....NO TEST DATA AVAILABLE....

61340 TAPE KAPTON/AL METALIZED KN80

MANF: ORCON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.006	0.003		00.60	SMALL
A	1	025.9	014.3	0.006	0.003		00.20	SMALL
A	1	030.0	009.0	0.006	0.003		00.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.57	3.45	.73	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.51	

63948 TAPE KAPTON/DACRON/CHEMGLAZE GID: BFFJCD

MANF: RCA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.008		00.10	12.00	T NONE
C	1	025.9	014.3	0.008		01.90	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61224 TAPE KAPTON/GLASS/SILICONE JE4.10 GID: DYCDCK

MANF: CONN HARD RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.5E-6	1.28	.35		24H-257F-0psia3.5E-6

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

06471 TAPE KAPTON/NYLON ACRYLIC KN80 GID: ABCDAK

MANF: ORCON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.006	0.003		01.20	SMALL
A	1	030.0	010.0	0.004	0.003		02.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	1.20	.24	.57	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE
No test data		

61586 TAPE KAPTON/NYLON ACRYLIC LOT 20 GID: FJAKXX

MANF: ORCON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.004	0.003		01.20	NONE
A	1	030.0	010.4	0.004	0.003		01.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.1E-6	1.27	.21	.64	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.30	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006537 5

61686 TAPE KAPTON/NYLON OT21 GID: DZAKBS

MANF: ORCON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.004	0.003		02.20	SMALL
A	1	025.9	014.3	0.004	0.003		03.50	SMALL
A	1	030.0	010.4	0.004	0.003		02.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.2E-6	8.86	4.93	.57	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.48	

62304 TAPE KAPTON/POLYIMIDE 583 GID: DYCDXX

MANF: TAPECON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.2E-6	3.13	.17	.34	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

06186 TAPE KAPTON/SILICONE K350 PS GID: DZXXXX

MANF: CONN HARD RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00022.06	

20640 TAPE KEVLAR 2176-1 GID: DYXXXX

MANF: FABRIC RESEARCH LAB

....NO TEST DATA AVAILABLE....

63214 TAPE KEVLAR POLYURETHANE COATED GID: DYJHCQ

MANF: WESTERN FILAMENT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.015			02.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65520 TAPE L-T-90D/SCOTCH 800 GID: DXXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.003	0.003		05.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00022.19	

69860 TAPE LACING (PORTION FROM HYDROCARBON SAMPLE LINE)

MANF: NASA/KSC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.97	.12	.10	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

06051 TAPE LACING S199 POLYIMIDE GID: ECCDCO

MANF: FABRIC RESEARCH LAB

SPEC: SE-C-0093

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.035			02.10	NONE
A	2	023.8	014.5	0.022			00.10	NONE
A	1	023.8	014.5	0.022			04.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	1.10	.01		16H-248F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.13	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006538 7

06051 TAPE LACING S199 POLYIMIDE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
					24H-70F-

ODOR / TOXICITY

RT	RT	WEIGHT	CURE

65453 TAPE LATEX ST10 GID: DYACXX

MANF: SHAMROCK CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	0.006		00.60	12.00	T NONE
I	1	025.9	014.5	0.006		00.80	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	K	00022.46	

61934 TAPE LEAD FOIL 420 GID: DZMPXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.006	0.003		04.70	NONE
C	1	025.9	014.3	0.006	0.003	00.44	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.85	.14		

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
No test data			

62414 TAPE LETTERING 3M GID: DZXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.002			01.20	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	V	00009.99	

60394 TAPE LOOP GID: DYXXXX

....NO TEST DATA AVAILABLE....

20430 TAPE LOOP-TAPE GORTEX GID: DYCBXX

MANF: BALLY RIBBON MILLS SPEC: ST13P707-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.024			01.70	NONE
A	1	033.0	014.3	0.024			01.80	NONE
C	1	100.0	020.2	0.024		00.44	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	9.0E-7	.04	.00		

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	V	00020.54	

20505 TAPE LOOP-TAPE KEVLAR 1759 GID: DYJHXX

MANF: BALLY RIBBON MILLS SPEC: ST12W044-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.058			01.00	NONE
B	1	033.0	014.3	0.058			06.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.2E-7	2.95	.16		

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	A	00020.09	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006539 9

20389 TAPE LOOP-TAPE KEVLAR 2176 GID: DYJHXX

MANF: BALLY RIBBON MILLS SPEC: ST13W044-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.082			01.80	NONE
A	1	025.9	014.3	0.035			04.90	NONE
A	1	025.9	014.3	0.041			02.70	NONE
C	2	033.0	004.3	0.035			01.70	NONE
C	1	033.0	004.3	0.035		00.20	12.00 T	NONE
C	2	033.0	014.3	0.041			00.60	NONE
C	1	033.0	014.3	0.041		00.07	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	9.0E-7	3.50	.24		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.49	

20791 TAPE LOOP-TAPE NOMEX GID: DYBVXX

MANF: BALLY RIBBON MILLS SPEC: MIL-W-81116B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3				00.20	NONE
C	1	025.9	014.3			00.19	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00019.68	

61919 TAPE LOOP-TAPE NYLON 1234 GID: BOBSXX

MANF: BALLY RIBBON MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.061			08.20	NONE
X	1	023.8	014.5	0.061		00.19	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.7E-6	1.87	.22		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00035.20	

65265 TAPE MANCO FIREGUARD FRD60 GID: DZCUXX

MANF: MANCO INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.010	0.003	00.25	06.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	17.76	12.94	.04	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00021.73	

61500 TAPE MARKING 02

MANF: SPEC: MIL-STD-1247B

....NO TEST DATA AVAILABLE:...

62388 TAPE MEASURE ERWIN PC10 GID: FCXXXX

MANF: ERWIN CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00087.18	

80261 TAPE MOLDED HOOK ULTEME PLASTIC EX1 GID: DYXXXX

MANF: FOSTER MILLER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.116		00.09	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006540 5

60381 TAPE MX4703-2 GID: DYXXXX
MANF: JOHNS-MANVILLE SPEC: USBI99605-0010
....NO TEST DATA AVAILABLE....

06479 TAPE MYLAR 444 FILM ACRYLIC ADHESIVE GID: DYAKXX
....NO TEST DATA AVAILABLE....

60491 TAPE MYLAR 49/SILICONE GID: DYCNIA
MANF: TUCK INDUSTRIES

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	A	00020.46	

60826 TAPE MYLAR ALUMINIZED GID: DYCCFJ
MANF: MEYER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.002	0.003	00.00	00.00	NONE
B	1	023.8	014.5	0.002	0.003		07.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	5.68	1.80		

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	K	00006.50	

60998 TAPE MYLAR INS102 ALUMINIZED GID: DZFJCC
MANF: UNKNOWN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.003		04.60	NONE
A	1	030.0	009.0	0.003	0.003		03.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	V	00003.85	

06525 TAPE MYLAR M69 WITH ACRYLIC ADHESIVE GID: DZXXXX
MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	030.0	010.0	0.005		00.00	00.00	NONE
B	1	030.0	010.0	0.005		0.5	07.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.68	.01	.00	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	A	22.031	

20383 TAPE MYLAR PS ADHESIVE GID: DYCBXX
MANF: MEYER CO SPEC: ST90M078-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.002			06.50	MOD
A	1	025.9	014.3	0.002	0.003		05.40	NONE
B	1	033.0	014.3	0.002	0.003		06.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.27	1.03	.00	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	A	00003.19	

05241 TAPE MYLAR/ACRYLIC PS ADHESIVE GID: DYCCAK
MANF: WESTERN SINCLAIR SPEC: MIL-T-9906 MIL-T-9906A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.004		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006541 7

05241 TAPE MYLAR/ACRYLIC PS ADHESIVE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.004			01.60	NONE
B	1	024.5	014.3	0.005	0.003	00.18	07.50	NONE
I	1	025.9	014.3	0.004	0.003	00.27	12.00	T SMALL
B	1	030.0	009.0	0.005			06.20	NONE
I	1	033.0	014.3	0.004	0.003	00.44	12.00	T SMALL

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.8E-6	1.26	.01		

ODOR

RT	RT	WEIGHT	CURE
A	X	00016.15	

TOXICITY

62484 TAPE MYLAR/POLYESTER PS GID: DZCBCC

MANF: MEYERCORD CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	030.0	009.0	0.002	0.003		07.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.46	.09	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

63510 TAPE MYLAR/SILVER ADHESIVE GID: DYFJXX

MANF: SPEC: MM5DS-V156-78

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.002		00.00	00.00	NONE
C	1	025.9	014.3	0.002		00.41	12.00	T SMALL
I	1	030.0	010.0	0.002		00.42	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00017.19	

TOXICITY

61968 TAPE MYSTIK 6375 PAPER/PS GREEN GID: DZGMXX

MANF: BORDEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.006	0.003		03.70	NONE
C	1	025.9	014.3	0.006	0.003	00.85	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	X	00023.19	

TOXICITY

05150 TAPE MYSTIK 6402 PROPYLENE/ACRYLIC ADHESIVE GID: DYCGAK

MANF: BORDEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.003		00.00	00.00	NONE
A	1	023.8	014.5	0.003			03.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.45	.02		

ODOR

RT	RT	WEIGHT	CURE
A	X	00006.97	

TOXICITY

05363 TAPE MYSTIK 6466 DOUBLE COATED ADHESIVE GID: DZCCHD

MANF: BORDEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.007	0.003		05.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006542 9

05363 TAPE MYSTIK 6466 DOUBLE COATED ADHESIVE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.014	0.003	01.99	12.00	T SMALL

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.00	2.02	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00012.02	

61566 TAPE MYSTIK 7000 GLASS/SILICONE ADHESIVE GID: DZCKIA

MANF: BORDEN SPEC: MIL-I-19166

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.010			01.50	NONE
A	1	025.9	014.3	0.010	0.003		02.30	NONE
A	1	030.0	010.4	0.010	0.003		02.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.34	1.58	.00	2H-257F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00036.60	

61567 TAPE MYSTIK 7001 GLASS/SILICONE ADHESIVE GID: DYCKIA

MANF: BORDEN SPEC: MDM1892 MIL-I-19166

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.008	0.003		00.30	NONE
A	1	025.9	014.3	0.007	0.003		01.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-7	.65	.34		

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	31.50	

05599 TAPE MYSTIK 7100 GLASS/SILICONE ADHESIVE GID: DZIACK

MANF: BORDEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.013	0.003		00.10	NONE
C	1	023.8	014.5	0.013	0.003	00.32	11.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.60	.79	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00054.66	

60441 TAPE MYSTIK 7321 MYLAR/SILICONE GID: DZCJXX

MANF: BORDEN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.45	.49	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00020.67	

62451 TAPE MYSTIK 7341 POLYESTER/ACRYLIC ADHESIVE GID: DYCBAK

MANF: BORDEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.003	0.003	00.00	00.00	NONE
A	1	020.9	014.7	0.003	0.003		06.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.65	.01	.00	

ODOR

RT
No test data.

TOXICITY

RT	RT WEIGHT	CURE

05085 TAPE MYSTIK 7361 KAPTON/SILICONE ADHESIVE GID: DZCDCK

MANF: BORDEN

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006543 0

05085 TAPE MYSTIK 7361 KAPTON/SILICONE ADHESIVE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.003		02.50	NONE
A	1	033.0	014.3	0.003	0.003		02.00	NONE
X	1	100.0	020.2	0.003	0.003	01.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.20	.03	.00	24H-302F-0psiaVACUUM

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.08	

TOXICITY

05086 TAPE MYSTIK 7366 KAPTON/SILICONE ADHESIVE GID: DYCKXX

MANF: BORDEN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.45	1.68	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05294 TAPE MYSTIK 7367 KAPTON/ACRYLIC ADHESIVE GID: DYCDXX

MANF: BORDEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		02.40	NONE
A	1	030.0	010.0	0.003	0.003		04.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.65	.02	.00	24H-199F-

ODOR

RT	RT	WEIGHT	CURE
A	V	00010.61	

TOXICITY

61065 TAPE MYSTIK 7367/DC3140 COATING GID: DZCDAK

MANF: BORDEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.014	0.003		10.20	NONE
A	1	023.8	014.5	0.015	0.003		05.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	V	00044.16	168H-70F-

TOXICITY

00718 TAPE MYSTIK 7402 ALUMINUM SILICONE ADHESIVE GID: DYFKCK

MANF: BORDEN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.09	.54	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60370 TAPE MYSTIK 7452 ALUMINUM/ACRYLIC ADHESIVE GID: DZFKAK

MANF: BORDEN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.37	.04	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05177 TAPE MYSTIK 7453 AL ADHESIVE GID: DYFXXX

MANF: BORDEN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005			01.30	SMALL
A	1	025.9	014.3	0.005	0.003		00.70	NONE
A	1	033.0	014.3	0.005	0.003		00.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.64	.04	.00	

ODOR

RT	RT	WEIGHT	CURE
A	X	00020.35	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006544 2

02897 TAPE MYSTIK 7455 ADHESIVE GID: DZMACK

MANF: BORDEN

SPEC: MB0135-020

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.011			06.00	NONE
A	1	020.9	014.7	0.115			02.00	NONE
A	1	020.9	014.7	0.005	0.076	00.00	00.00	NONE
A	1	025.9	014.3	0.004	0.003		00.11	NONE
A	1	025.9	014.3	0.006	0.003		01.80	NONE
X	1	030.0	009.0	0.004	0.003		01.20	MOD
A	1	033.0	014.3	0.006	0.003		01.90	NONE
X	1	100.0	014.3	0.006	0.003	00.14	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

MB0135-062

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.82	2.62	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00023.45	

05140 TAPE MYSTIK 7503 TFE/SILICONE ADHESIVE GID: DZCNCK

MANF: BORDEN

SPEC: MIL-I-23594A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.005		00.50	12.00	T NONE
A	1	023.8	014.5	0.005	0.003		02.30	NONE
I	1	023.8	014.5	0.009		00.27	12.00	T NONE
A	1	025.9	014.3	0.004	0.003		02.40	NONE
A	1	030.0	010.0	0.010	0.003	00.013	02.10	NONE
A	1	033.0	014.3	0.004	0.003		02.50	NONE
C	1	100.0	017.0	0.004	0.003	00.35	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.63	.07	.00	2H-199F- 3H-390F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00026.61	24H-150F-

62085 TAPE HELTAPE 100 TRANSFER GID: DZXXXX

MANF: DIELECTRIC POLYMERS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	7.2E-7	3.46	.00		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00014.56	

62101 TAPE HELTAPE 410 TRANSFER GID: DZXXXX

MANF: DIELECTRIC POLYMERS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.2E-7	2.90	.00		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00020.61	

06447 TAPE HM53-57 KAPTON/AL ORGANIC COATED GID: DYCDMA

MANF: NATIONAL METALLIZING

SPEC: MB0135-050T5

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.003	0.003		03.40	NONE
A	1	025.9	014.3	0.003	0.003		05.00	NONE
B	1	030.0	009.0	0.003	0.003	00.35	07.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.93	.00	.21	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

20577 TAPE NOMEX 1229 GID: DYBVXX

MANF: BALLY RIBBON MILLS

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006545 4

20577 TAPE NOMEX 1229 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.075		00.08	12.00	T NONE
C	2	025.9	014.3	0.093			00.10	NONE
C	1	025.9	014.3	0.093		00.09	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.9E-6	5.77	.18		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.85	

20293 TAPE NOMEX 9476 GID: DYBVXX

MANF:

SPEC: MIL-T-5038T3

....NO TEST DATA AVAILABLE....

20737 TAPE NOMEX 9650 GID: DYBVXX

MANF: BALLY RIBBON MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.040			00.10	NONE
C	1	025.9	014.3	0.040		00.14	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.22	

63227 TAPE NOMEX RF466/COATING VITON B50 GID: DYBVXX

MANF: GOODYEAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.025			03.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62705 TAPE NOMEX UTILITY FR PS ADHESIVE GID: DYBVGM

MANF: A D LITTLE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003		02.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.2E-6	2.74	.44		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00012.58	

20322 TAPE NYLON 6707 GID: DYCDBV

MANF: BALLY RIBBON MILLS

SPEC: ST13N072-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.014			03.70	NONE
X	1	025.9	014.3	0.014			05.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.1E-7	1.21	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00010.09	

63228 TAPE NYLON WEBBING WHITE GID: DYBSXX

MANF:

SPEC: MIL-T-5038

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.017			02.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63230 TAPE OKONITE 35 JACKETING GID: DYXXXX

MANF: OKONITE CO

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006546 6

63230 TAPE OKONITE 35 JACKETING (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7				04.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61893 TAPE P051 ACRYLIC TRANSFER GID: DZAKXX

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.004	0.003	00.00	00.00	NONE
B	1	020.9	014.7	0.004	0.003		06.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.36	.03	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

80284 TAPE P100 ALUMINUM FOIL/GLASS CLOTH WITH SILICONE ADHESIVE GID: DYXXXX

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.006	0.003	0.04	01.25	NONE
A	1	025.9	014.3	0.008	0.032	0.009	00.25	NONE
A	1	030.0	009.0	0.006	0.003	0.05	01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63231 TAPE P11 ALUMINUM FOIL GID: DYFKXX

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.005			00.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.36	.01	.00	

ODOR

RT	RT WEIGHT	CURE
X	00020.90	

TOXICITY

80055 TAPE P21 GLASS GID: DYGDXX

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.007	0.003		05.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.35	.34	.00	1H-300F-

ODOR

RT	RT WEIGHT	CURE
K	22.232	

TOXICITY

06118 TAPE P211 GLASS/SILICONE ADHESIVE GID: EBFVCK

MANF: PERMACEL SPEC: MIL-T-19166

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.006	0.003		02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	72	-297	0.006	3	04
X	MECH	14.7	72	-297	0.006	3	4

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.8E-7	1.22	.43		

ODOR

RT	RT WEIGHT	CURE
A	K 00026.18	

TOXICITY

06133 TAPE P212 GLASS/SILICONE ADHESIVE GID: EPFVCK

MANF: PERMACEL SPEC: MIL-I-19166

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.007	0.003		02.70	NONE
A	1	033.0	014.3	0.007	0.003		03.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	14.7	72	-297	0.008	02	02

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006547 8

06133 TAPE P212 GLASS/SILICONE ADHESIVE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.6E-7	2.10	.70		

ODOR

RT	RT	WEIGHT	CURE
A	V	00031.01	

TOXICITY

No test data

61139 TAPE P213 GLASS ACRYLIC ADHESIVE GID: DYAKIA

MANF: PERMACEL SPEC: STM0711-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.008		00.40	12.00 T	NONE
A	1	025.9	014.3				02.62	NONE
A	1	030.0	009.0				03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.77	.14	.00	

ODOR

RT	RT	WEIGHT	CURE
	A	00018.28	

TOXICITY

64290 TAPE P214 GLASS/ACRYLIC GID: DYIAAK

MANF: PERMACEL SPEC: MIL-I-15126

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.0E-6	6.65	3.38	.16	

ODOR

RT	RT	WEIGHT	CURE
	A	00018.90	

TOXICITY

05261 TAPE P221 KAPTON WITH SILICONE ADHESIVE GID: DZCDCK

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002		00.11	03.00	NONE
A	1	023.8	014.5	0.003	0.003		01.60	NONE
A	1	030.0	010.0	0.003	0.003		01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.30	.63	.00	48H-302F-0psiaVACUUM

ODOR

RT	RT	WEIGHT	CURE
	X	00010.67	

TOXICITY

61149 TAPE P223 TEFLON/AG GID: DYCNGQ

MANF: PERMACEL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.80	.73	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05575 TAPE P224 KAPTON/ACRYLIC ADHESIVE GID: DZCDAK

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.003	0.003	0.24	06.00	NONE
A	1	023.8	014.5	0.003	0.003		02.40	NONE
B	1	025.9	014.3	0.003	0.003	0.26	06.50	NONE
B	1	030.0	009.0	0.003		0.29	07.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.62	.03		1H-300F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05234 TAPE P252 MYLAR PS GID: DZCCHD

MANF: PERMACEL SPEC: MIL-I-15126MFT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.51	.37	.00	.5H-300F-

ODOR

RT	RT	WEIGHT	CURE
A	K	00009.05	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006548 T

80287 TAPE P262 NOMEX ARAMID FLATBACK ELEC INSULATION/SILICONE ADHESIVE GID: DYXXXX

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.004	0.003	00.12	03.50	NONE
B	1	025.9	014.3	0.004	0.003	0.27	07.50	NONE
B	1	030.0	009.0	0.004	0.003	0.12	08.30	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.96	3.58	.00	2H-275F-

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

80189 TAPE P263 NOMEX/ACRYLIC (CREPE) GID: DYXXXX

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.017	0.003	0.07	06.50	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.0E-6	9.52	3.84	1.27	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
K	16.47	

TOXICITY

85409 TAPE P2650 SILICONE RUBBER NON ADHESIVE SPEC: MMS-J-517

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.015	0.003		03.50	NONE
A	1	020.9	014.7	0.010	0.003		03.75	NONE
A	1	030.0	010.2	0.015	.003		01.25	NONE
A	1	030.0	010.2	0.01	.003		01.00	NONE
A	1	24.5	14.5	.015	.003		5.25	NONE
B	1	24.5	14.5	.01	.003		7.25	NONE
B	1	25.9	14.3	.015	.003		7.5	NONE
B	1	25.9	14.3	.01	.003		7.5	NONE
B	1	30.0	10.2	.015	.003		8.25	NONE
B	1	30.0	10.2	.01	.003		8.5	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63243 TAPE P29 VINYL BLACK ELECTRIC GID: EBCUXX

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.007		00.50	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63235 TAPE P421 TEFLON SILICONE ADHESIVE GID: DYCOCK SPEC: MIL-I-23594T1

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7				03.00	NONE
A	1	020.9	020.9	0.007	0.003	00.11	01.80	NONE
A	1	025.9	014.3	.0065	0.003		04.50	NONE
A	1	030.0	009.0	0.005	0.003	00.11	03.25	NONE
A	1	30.0	10.2	.0065	.003		5.02	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.21	5.23		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

80278 TAPE P422 TEFLON/SILICONE GID: DYXXXX

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
[illegible]							10.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006549 1

80278 TAPE P422 TEFLON/SILICONE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.25	.10	.00	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

05692 TAPE P423 TFE/SILICONE GID: DYCOCK

MANF: PERMACEL

SPEC: MIL-I-2394 T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.004	0.003		00.10	NONE
X	1	023.8	014.5	0.004	0.003		05.70	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-7	.83	.41		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
K	00020.01	

80315 TAPE P424 TEFLON

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.013	.003		02.50	NONE
A	1	025.9	014.3	0.013	0.003		04.25	NONE
A	1	30.0	10.2	.013	.003		5.0	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

85485 TAPE P427 TEFLON

MANF: PERMACEL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.0E-6	.63	.27	.06	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

80286 TAPE P430 TEFLON WITH PS GID: DYXXXX

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.003	0.003	0.35	09.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.14	.01	.05	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

85486 TAPE P440 TEFLON/GLASS

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.2	0.006	0.003		04.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	.58	.21	.05	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

06406 TAPE P50 COTTON WITH RUBBER ADHESIVE GID: PYFSHD

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.012			00.10	NONE
C	1	020.9	014.7	0.012		00.27	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

80285 TAPE P5001 SILICONE RUBBER/GLASS CLOTH/SILICONE ASH GID: DYXXXX

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.015	0.003	0.08	02.25	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006550 8

80285 TAPE P5001 SILICONE RUBBER/GLASS CLOTH/SILICONE ASH (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.016	0.002	0.005	00.13	NONE
A	1	030.0	009.0	0.015	0.003	0.10	03.13	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.0E-6	1.38	.58	.07	

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

62462 TAPE P551B SILICONE GID: DYCKXX

MANF: PERMACEL

SPEC: HAC 90827

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-6	4.80	.18		.5H-300F- 4H-400F-

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

85484 TAPE P670 POLYETHYLENE

MANF: PERMACEL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	2.48	.46	.35	

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

80150 TAPE P69 PS

MANF: PERMACEL

SPEC: STM-M-173

....NO TEST DATA AVAILABLE....

60194 TAPE PACKAGING VINYL WHITE GID: DYXXXX

MANF:

SPEC: PPP-T-66E T2

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	26.71	5.77	.00	

ODOR

RT	RT WEIGHT	CURE

No test data

TOXICITY

60110 TAPE PAPER BACKED

MANF:

SPEC: MIL-I-15126

....NO TEST DATA AVAILABLE....

20554 TAPE PAPER DOUBLEFACE PSA

MANF: AQM

....NO TEST DATA AVAILABLE....

65522 TAPE PLASTIC GID: DYXXXX

MANF: OAK INDUSTRIES

SPEC: MMS-F-417

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297		00	20

20891 TAPE POLYESTER 415/ACRYLIC ADHESIVE GID: DZCBAK

MANF: 3M CO
DUPONT

SPEC: MB0125-071

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.004			02.90	NONE
I	2	023.8	014.5	0.009		00.07	10.50	T SMALL

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.96	.11	.00	

ODOR

RT	RT WEIGHT	CURE
A	X 00020.17	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006551 T

20335 TAPE POLYESTER LOOP 2297 GID: DYCBXX
MANF: BALLY RIBBON MILLS SPEC: ST13P133-01

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	023.8	014.5	0.022			04.40	MOD	No test data	No test data							
X	1	023.8	014.5	0.022		00.28	12.00	T MOD									
X	2	025.9	014.3	0.025		00.06	12.00	T MOD									
X	1	025.9	014.3	0.025		00.30	12.00	T MOD									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	7.1E-7	.41	.12			A	V	00020.10	

20120 TAPE POLYESTER/GLASS 76593 GID: DYCBGD
MANF: GENERAL ELECTRIC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	023.8	014.5	0.008		00.08	12.00	T NONE	No test data	No test data							
C	1	023.8	014.5	0.008		01.30	12.00	T NONE									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
I	2.0E-6	2.02	.81			A	X	00014.99	

63997 TAPE POLYETHYLENE CW3 GID: DYCFAK
MANF: MANCO INC

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.010	0.003	00.00	00.00	NONE	No test data	No test data							
X	1	025.9	014.3	0.010	0.003	00.10	12.00	T MOD									

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data						A	X	00020.55	

06096 TAPE POLYIMIDE AU/AL PS ADHESIVE GID: DZFJCD
MANF: NATIONAL METALLIZING SPEC: MB0135-050T4 MB0135-050T5
SHELDAHL

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	00022.45	

64176 TAPE POLYIMIDE PS GID: DYXXXX
MANF: FRALOCK SPEC: STM 0695-03

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.003			03.83	NONE	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY		
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
No test data							A	00003.93	

06218 TAPE POLYIMIDE PS ADHES GID: DYCDXX
....NO TEST DATA AVAILABLE....

06095 TAPE POLYIMIDE T966 GID: DYCDAK
MANF: FRALOCK SPEC: MB0135-050T3 MB0135-050T5
NATIONAL METALLIZING

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.003			02.50	NONE	No test data	No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006552 1

06095 TAPE POLYIMIDE T966 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.003			02.50	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.0E-6	.75	.01	.66	

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
V	00009.54	

05594 TAPE POLYIMIDE X1156/SILICONE ADHESIVE GID: DVCKCD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.36	.25	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE

No test data

20563 TAPE POLYIMIDE/SILICONE K100 GID: DYCKXX

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.003		02.30	NONE
A	1	030.0	009.0	0.003	0.003		01.40	SMALL
B	2	033.0	014.3	0.004	0.003		00.30	NONE
B	1	033.0	014.3	0.004	0.003		06.30	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.75	.60	.00	24H-151F-0psiaVACUUM

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00019.48	

61935 TAPE POLYKEN 207 COTTON GID: DZFSXX

MANF: KENDALL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.013	0.003		00.40	NONE
C	1	025.9	014.3	0.013	0.003	00.44	12.00 T	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	K 00038.86	

61898 TAPE POLYKEN 224A GID: DZXXXX

MANF: KENDALL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.011	0.003	00.11	12.00 T	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	K 00036.26	

61899 TAPE POLYKEN 234A GID: DZXXXX

MANF: KENDALL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.013		00.17	12.00 T	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	K 00021.81	

62404 TAPE POLYPENCO 2003 PTFE GID: DYCNXX

MANF: POLYPENCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.007	0.003		01.70	NONE

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

No test data

62404 TAPE POLYPENCO 2003 PTFE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.42	.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20456 TAPE POLYPROPYLENE P910 GID: DYCGXX

MANF: PERMACEL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.002		00.00	00.00	NONE
B	1	025.9	014.3	0.002			08.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.2E-7	.91	.03		

ODOR

RT	RT WEIGHT	CURE
A	X 00017.21	

TOXICITY

60154 TAPE POLYURETHANE/ADHESIVE BACKNG 4000SE GID: DYXXXX

....NO TEST DATA AVAILABLE....

62014 TAPE PS ADHESIVE GID: DZXXXX

MANF: TUCK INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.007		00.13	11.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	9.0E-7	1.28	.35		

ODOR

RT	RT WEIGHT	CURE
A	A 00027.53	

TOXICITY

61967 TAPE PS C706 BLUE GID: DZXXXX

MANF: ARNO PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.011	0.003		05.90	SMALL
B	1	025.9	014.3	0.015	0.003	00.24	10.00	NONE
B	1	033.0	014.3	0.013	0.003	00.42	07.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	8.2E-7	3.48	.95		24H-70F-

ODOR

RT	RT WEIGHT	CURE
A	A 00018.74	

TOXICITY

64866 TAPE PTFE (EXPANDED) GID: DYCOXX

MANF: W L GORE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	K 00020.68	

TOXICITY

80152 TAPE PTFE EXPANDED/NON ADHESIVE

MANF: W L GORE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.02	.00	.01	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62883 TAPE PTFE SEALANT 48 GID: DYCOXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	150	72	-220	0.003	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006554 5

62252 TAPE PVF OT6 GID: DYHCXX
MANF: HI TEMP INSULATION

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.004	0.003		04.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	12.26	7.39	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20150 TAPE REFLECTIVE
MANF: 3M CO
....NO TEST DATA AVAILABLE....

61851 TAPE REINFORCED 536-34-2 GOLD GID: DYCKMU
MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5		0.003	00.00	00.00	NONE
A	1	023.8	014.5		0.003		00.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.8E-6	1.09	.54		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60653 TAPE RETROREFLECTIVE 3870 GID: DYXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.004	0.003		07.90	NONE
I	1	025.9	014.3	0.010	0.003	00.49	11.70 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
V	00002.72	

TOXICITY

85472 TAPE RL2168A ASBESTOS COATED WITH BUTYL RUBBER GID: DYXXXX
MANF: RM ENGINEERED PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.060	0.003	00.05	9.25	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65126 TAPE RUBBER FLUOREL L2231 GID: DYDEXX
MANF: PASSAIC RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	0.050		00.10	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-6	2.13	.27	.03	

ODOR

RT	RT WEIGHT	CURE
X	00021.61	

TOXICITY

20175 TAPE SAFETY WALK ANTI-SLIP GID: AKXXXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.030	0.063	00.00	00.00	NONE
X	2	025.9	014.3	0.046	0.003	00.01	06.90	MOD
X	1	025.9	014.3	0.046	0.003	00.06	12.00 T	MOD
X	2	025.9	014.3	0.043	0.003	00.02	12.00 T	MOD
X	1	025.9	014.3	0.043	0.003	00.10	12.00 T	MOD

FSC

RT	FLUID NAME
A	HYD

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.1E-7	1.24	.46		

ODOR

RT	RT WEIGHT	CURE
A	00027.43	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006555 7

60345 TAPE SCOTCH 1157 GID: DYXXXX

MANF: 3M CO

....NO TEST DATA AVAILABLE....

06122 TAPE SCOTCH 1170 ALUMINUM FOIL CONDUCTIVE ACRYLIC ADHESIVE GID: DZFKAK

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.004			00.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.23	.04	.00	24H-302F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06241 TAPE SCOTCH 118 COPPER WITH ACRYLIC ADHESIVE GID: DYAKHK

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.004	0.003		05.10	NONE
A	1	033.0	014.3	0.004	0.003		04.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00019.29	

TOXICITY

65185 TAPE SCOTCH 1181 GID: DYHNAK

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	00.29	00.13	00.02	24H-77F-
					1H-145F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05586 TAPE SCOTCH 1245 CU WITH SILICONE ADHESIVE GID: DZMCCK

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.004	0.003		01.60	NONE
I	1	023.8	014.5	0.008		00.83	12.00	T NONE
A	1	030.0	010.0	0.004	0.003		04.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.13	.09	.00	72H-257F-0psia10E-3 TORR

ODOR

RT	RT WEIGHT	CURE
A	A 00020.60	

TOXICITY

06243 TAPE SCOTCH 1267 AL/ACRYLIC/ADHESIVE GID: DYMAAK

MANF: 3M CO SPEC: MIL-W-81044

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.007	0.003		02.80	NONE
A	1	030.0	010.0	0.010	0.003		01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.27	.11	.00	72H-257F-0psia10E-3 TORR

ODOR

RT	RT WEIGHT	CURE
	K 00021.64	

TOXICITY

06326 TAPE SCOTCH 27 GLASS/RUBBER/ADHESIVE GID: DYIAHD

MANF: 3M CO SPEC: MIL-I-15126TGFT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.006	0.003	00.00	00.00	NONE
B	1	020.9	014.7	0.006	0.003		06.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006556 9

06326 TAPE SCOTCH 27 GLASS/RUBBER/ADHESIVE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.8E-7	2.99	.94	.09	

ODOR

RT	RT	WEIGHT	CURE
A	V	00020.70	

TOXICITY

05879 TAPE SCOTCH 3 ELECTRIC GID: CKCNXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.005	0.003	00.00	00.00	NONE
C	1	023.8	014.5	0.005	0.003	00.80	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.4E-6	4.21	.22		

ODOR

RT	RT	WEIGHT	CURE
A	V	00015.41	

TOXICITY

05937 TAPE SCOTCH 3082 TEFLON GID: DYCNXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005			02.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.01	.00	.00	

ODOR

RT	RT	WEIGHT	CURE
A	A	00008.70	

TOXICITY

60373 TAPE SCOTCH 346 DOUBLE COAT PS GID: DYXXXX

MANF: 3M CO SPEC: MMCJ536B

....NO TEST DATA AVAILABLE....

06188 TAPE SCOTCH 361 GLASS/SILICONE/ADHESIVE GID: DYIACK

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.006	0.003		02.20	NONE
I	1	025.9	014.3	0.007		01.13	12.00 T	NONE
A	1	025.9	014.3	0.006	0.003		00.50	SMALL
A	1	030.0	010.4	0.006	0.003		01.40	SMALL
A	1	030.0	010.0	0.006	0.003		01.80	SMALL
A	1	030.0	010.0	0.007	0.003		01.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.9E-6	1.06	.41	.05	

ODOR

RT	RT	WEIGHT	CURE
	A	00013.50	

TOXICITY

00385 TAPE SCOTCH 363 REFLECTIVE GID: DZCKEJ

MANF: 3M CO SPEC: MB0135-020

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.008	0.003		01.10	NONE
A	1	030.0	009.0	0.008	0.003		05.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	2.56	1.22	.00	

ODOR

RT	RT	WEIGHT	CURE
A	A	00019.38	

TOXICITY

62019 TAPE SCOTCH 380 COTTON GID: DZFSXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.009	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006557 0

62019 TAPE SCOTCH 380 COTTON (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	025.9	014.3	0.009	0.003	00.38	12.00	T SMALL

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-7	4.13	1.01		24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00027.05	

65036 TAPE SCOTCH 390 POLYETHYLENE GID: DZCFXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.010	0.003	00.20	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
	K 00022.56	

61461 TAPE SCOTCH 425 PS GID: DYFKAK

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.009	0.003		01.50	NONE
A	1	023.8	014.5	0.005	0.003		01.50	SMALL
A	1	025.9	014.3	0.009		00.00	00.00	NONE
A	1	030.0	010.0	0.005	0.003		02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70	0.005	0	20
Z	MECH	1500	60	70	0.005	1	12

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.24	.03	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
	K 00043.80	

06327 TAPE SCOTCH 428 ALUMINUM FOIL/RUBBER ADHESIVE GID: DYCKFJ

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.03	.61	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

06123 TAPE SCOTCH 433 ALUMINUM FOIL WITH SILICONE ADHESIVE GID: DZCKXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.004	0.003		00.20	NONE
A	1	030.0	009.0	0.004	0.003		00.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.53	.26	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.30	

64325 TAPE SCOTCH 438 GID: DYXXXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
	K 00002.02	

60590 TAPE SCOTCH 444 POLYESTER DOUBLE BACK GID: DYCBGM

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.004	0.003	00.00	00.00	NONE
B	1	025.9	014.3	0.004	0.003		08.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006558 2

60590 TAPE SCOTCH 444 POLYESTER DOUBLE BACK (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.6E-6	3.03	.63	.23	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00010.01	

05173 TAPE SCOTCH 465 ACRYLIC TRANSFER GID: DYAKXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.002	0.003	00.00	00.00	NONE
A	1	020.9	014.7	0.002	0.003		03.30	NONE
C	1	025.9	014.3	0.002	0.003	00.44	12.00	T NONE
A	1	030.0	010.0	0.003	0.003		05.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.84	.21	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00014.53	

61301 TAPE SCOTCH 467 GID: DZAKXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.003	0.003		06.20	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.11	.02		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00020.04	

60663 TAPE SCOTCH 468 GID: DZAKXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.004	0.003		09.50	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.89	.00	.00	24H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00010.66	24H-70F- 24H-150F-

60170 TAPE SCOTCH 471 GID: DYBYXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.30	2.91	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

61999 TAPE SCOTCH 474 GID: DYBYBG

MANF: 3M CO SPEC: PPP-T-66

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.007	0.003		02.90	NONE
A	1	023.8	014.5	0.007	0.003		04.50	NONE
X	1	030.0	010.0	0.010	0.003	00.40	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	3.7E-6	7.76	4.65		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00027.23	

05456 TAPE SCOTCH 48 TEFLON NO ADHESIVE GID: DYCOXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-6	.08	.03	.01	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006559 4

62377 TAPE SCOTCH 49 GID: EAFKXX
MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.1E-6	.17	.00	.05	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60429 TAPE SCOTCH 5 POLYESTER GID: DYCBXX
MANF: 3M CO
SPEC: MIL-I-15126F

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3			00.40	12.00	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.91	.10	.69	

ODOR

RT	RT WEIGHT	CURE
A	21.974	

TOXICITY

20766 TAPE SCOTCH 5201-8 EMBOSSING GID: DZXXXX
MANF: DYMO INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010	0.003		06.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05875 TAPE SCOTCH 53 POLYESTER GID: DYCBXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.002	0.003	00.00	00.00	NONE
C	1	023.8	014.5	0.002	0.003	00.28	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.03	.13	.00	2H-250F-

ODOR

RT	RT WEIGHT	CURE
A	A 00009.52	

TOXICITY

62541 TAPE SCOTCH 53 POLYURETHANE/SOLITHANE 113/300 GID: DYCBXX
MANF: 3M CO
THIOKOL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.7E-6	1.71	.19		24H-70F-

ODOR

RT	RT WEIGHT	CURE
A	B 00015.27	168H-70F- 24H-150F-

TOXICITY

20102 TAPE SCOTCH 54 POLYESTER PS GID: EBCBXX
MANF: 3M CO
SPEC: MIL-I-15126

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	020.9	014.7	0.002	0.003	00.00	00.00	NONE
B	1	020.9	014.7	0.002	0.003		06.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.75	.45	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05896 TAPE SCOTCH 5413 KAPTON WITH SILICONE ADHESIVE GID: DYCDXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		02.20	NONE
A	1	030.0	010.0	0.003	0.003		01.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.00	.13	.23	

ODOR

RT	RT WEIGHT	CURE
A	A 00022.74	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006560 0

06007 TAPE SCOTCH 5451 GID: DZFVCN

MANF: 3M CO SPEC: MB0135-059ALL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.011		00.05	12.00 T	NONE
A	1	020.9	014.7	0.006	0.003		01.10	NONE
A	1	025.9	014.3	0.007	0.003		01.80	NONE
A	1	030.0	009.0	0.007	0.003		03.70	NONE
A	1	030.0	010.0	0.006	0.003		01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.6E-6	.60	.62		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00025.77	

65264 TAPE SCOTCH 5453 TFE/SILICONE/GLASS GID: DZXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.010	0.003		01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	.45	.26	.02	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00021.86	

20751 TAPE SCOTCH 5480 TEFLON GID: DYCNXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.004	0.003	00.00	00.00	NONE
B	1	025.9	014.3	0.004	0.003		06.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.57	.28	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.02	

62366 TAPE SCOTCH 5491 SILICONE GID: DZCKXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.006	0.003		01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.2E-6	.22	.08	.05	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

63236 TAPE SCOTCH 56 POLYESTER GID: DYCBXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7			00.20	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.93	.69	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

60624 TAPE SCOTCH 567 GID: DZXXXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00003.06	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006561 2

20094 TAPE SCOTCH 57 POLYESTER GID: DYCBXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003		03.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.4E-7	1.92	.73		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00012.91	

05383 TAPE SCOTCH 583 ACRYLIC ADHESIVE GID: DZAKXX

MANF: 3M CO

SPEC: MIL-P-19834T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.002	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.002	0.003		02.00	NONE
A	1	030.0	010.0	0.003		00.338	03.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.50	.42	.00	.05H-300F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	V 00005.52	24H-70F- 24H-150F-

60185 TAPE SCOTCH 6 ACETATE GID: DZXXXX

MANF: 3M CO

....NO TEST DATA AVAILABLE....

06623 TAPE SCOTCH 60 TFE TEFLON/SILICONE GID: DYCKCN

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.004	0.003		05.60	NONE
A	1	030.0	010.4	0.004	0.003		04.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.78	.53	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	V 00020.82	

00543 TAPE SCOTCH 61 TFE/SILICONE PS GID: DZCNDS

MANF: 3M CO

SPEC: MIL-I-23594

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.006	0.003		02.90	NONE
A	1	030.0	010.0	0.006	0.003		02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1500		70	0.006	2	17

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.15	.08	.00	2H-500F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00022.27	

05319 TAPE SCOTCH 62 TFE/SILICONE PS ADHESIVE GID: EBCNDP

MANF: 3M CO

SPEC: MIL-I-23594T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.006			05.50	T SMALL
A	1	030.0	010.0	0.004			05.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.65	.03	.00	48H-212F-0psiaVACUUM

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	A 00019.90	

06092 TAPE SCOTCH 63 GID: DZCNAK

MANF: 3M CO

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006562 4 ■

06092 TAPE SCOTCH 63 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	023.8	014.5	0.003	0.003		02.80		NONE
A	1	025.8	014.3	0.003	0.003		04.30		NONE
A	1	030.0	014.3	0.003	0.003		06.00		NONE
I	1	033.2	015.5	0.003		00.37	12.00	T	NONE
B	1	035.0	014.3	0.003	0.003		06.20		NONE
B	1	040.0	014.3	0.003	0.003		07.00		NONE
X	1	050.0	014.3	0.003		00.41	12.00	T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	00.33	00.03	00.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62403 TAPE SCOTCH 635 POLYESTER GID: DYCBXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00019.92	

TOXICITY

06059 TAPE SCOTCH 64 TFE/GLASS/SILICONE GID: DZCNFV

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	020.9	014.7	0.006			01.40		NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06456 TAPE SCOTCH 666 PVC ACRYLIC ADHESVIE GID: DZXXXX

MANF: 3M CO SPEC: ST13T1393

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
C	2	025.9	014.3	0.004	0.003	00.00	00.00		NONE
C	1	025.9	014.3	0.004	0.003	00.34	12.00	T	SMALL
B	1	030.0	010.0	0.003		00.23	07.53		SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.12	.16	.00	

ODOR

RT	RT WEIGHT	CURE
X	00021.82	

TOXICITY

05822 TAPE SCOTCH 69 GLASS/SILICONE/ADHESIVE GID: DZCKIA

MANF: 3M CO SPEC: MIL-I-19166

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	023.8	014.5	0.008	0.003		02.20		NONE
A	1	030.0	010.0	0.008	0.003		00.20		NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.8E-7	2.13	1.34		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20193 TAPE SCOTCH 7321/49/56X1302 MYLAR/SILICONE GID: DYCKXX

....NO TEST DATA AVAILABLE....

05535 TAPE SCOTCH 74 POLYESTER/RUBBER GID: DYCDXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH		DRPBRN
A	1	023.8	014.5	0.001	0.003		02.50		NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.6E-7	1.25	.35		24H-150F-

ODOR

RT	RT WEIGHT	CURE
A	X 00002.93	24H-150F-

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006563 6

65260 TAPE SCOTCH 75-4280-0501-3-8005/ADHESIVE GID: DZXXXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00177.40	

TOXICITY

06536 TAPE SCOTCH 79 FIBERGLASS GID: DYFVXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.007	0.003		04.10	SMALL
A	1	025.9	014.3	0.007	0.003		05.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	1.82	1.18	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60476 TAPE SCOTCH 800 TEFLON PRESCRIPTION GID: DYXNCC

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.005			03.60	NONE
C	1	033.0	014.3	0.005		00.09	05.90	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.10	

TOXICITY

65455 TAPE SCOTCH 8210 LABEL GUARD GID: DYXXXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00016.21	

TOXICITY

63287 TAPE SCOTCH 838 TEDLAR GID: DYCJXX

MANF: 3M CO

SPEC: 9M03925

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.002			08.00	SMALL
B	2	020.9	014.7	0.003		00.00	00.00	NONE
B	1	020.9	014.7	0.003		00.40	06.50	SMALL
I	1	025.9	014.3	0.002		00.50	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00011.10	

TOXICITY

63252 TAPE SCOTCH 8417 CLEAR/8418 OPAQUE GID: DYXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.005	0.003	00.50	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06249 TAPE SCOTCH 850 POLYESTER/ACRYLIC ADHESIVE GID: DYCBCX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.005	0.003		05.70	NONE
C	2	020.9	014.7	0.002	0.003	00.00	00.00	NONE
C	1	020.9	014.7	0.002	0.003	00.30	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006564 8

06249 TAPE SCOTCH 850 POLYESTER/ACRYLIC ADHESIVE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.002	0.003	00.00	00.00	NONE
B	1	025.9	014.3	0.002	0.003		06.10	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.77	.02	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	A 00017.21	

06321 TAPE SCOTCH 853 POLYESTER GID: DYCBXX

MANF: 3M CO

SPEC: L-I-100 T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002	0.003		04.60	NONE
B	2	025.9	014.3	0.002		00.00	00.00	NONE
B	1	025.9	014.3	0.002			06.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	8.51	.08	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	X 00019.83	

62223 TAPE SCOTCH 861 ALUMINUM WITH PRESSURE SENSITIVE ADHESIVE GID: DZMAXX

MANF: LAMART CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.6E-6	.10	.00		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

05458 TAPE SCOTCH 92 SILICONE/POLYMIDE BACKING GID: DZCDCK

MANF: 3M CO

SPEC: RF 307435-92

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.006			04.30	NONE
A	1	023.8	014.5	0.005	0.003		06.10	NONE
A	1	023.8	014.5	0.003			01.40	NONE
X	1	030.0	010.0	0.003	0.003		02.10	MOD

FSC

RT	FLUID NAME
C	N204

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.79	.01	.00	24H-392F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	A 00010.66	

20726 TAPE SCOTCH 950 ACRYLIC TRANSFER GID: DYCBXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.005	0.003		06.60	NONE
X	1	025.9	014.3	0.005		00.19	00.60	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	4.14	1.06	.26	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

85493 TAPE SCOTCH 968

MANF: 3M CO

....NO TEST DATA AVAILABLE....

61282 TAPE SCOTCH MAGIC TRANSPARENT GID: DYAVXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	A 00009.54	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006565 T

05870 TAPE SCOTCH X1169 MYLAR GID: DYCBXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.002	0.003	00.00	00.00	NONE
C	1	023.8	014.5	0.002	0.003	00.29	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.29	.00	.06	

ODOR

RT	RT	WEIGHT	CURE
A	A	00008.82	

TOXICITY

05995 TAPE SCOTCH X1170 GID: DZXXXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.77	.25	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

64037 TAPE SCOTCH X1181 GID: DYXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	14.7	40	-297	0.008	00	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.92	.43	.00	24H-401F-0psiaVACUUM

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

05293 TAPE SCOTCH X1205 KAPTON WITH ACRYLIC ADHESIVE GID: DYCDAK

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.38	.02	.00	1H-257F-

ODOR

RT	RT	WEIGHT	CURE
A	V	00010.96	

TOXICITY

05254 TAPE SCOTCH X1252 POLYESTER PS ADHESIVE GID: DYCBXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.002	0.003		00.30	NONE
X	1	023.8	014.5	0.002	0.003		08.30	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.11	.03	.00	24H-70F-

ODOR

RT	RT	WEIGHT	CURE
A	V	00008.43	

TOXICITY

20702 TAPE SCOTCH Y427 ALUMINUM WITH ACRYLIC ADHESIVE GID: DYAKXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.005	0.003		02.10	NONE
A	1	033.3	014.3	0.005	0.003		01.60	NONE
A	1	100.0	020.2	0.005	0.003		00.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.2E-6	.21	.00		

ODOR

RT	RT	WEIGHT	CURE
A	A	00019.94	

TOXICITY

85411 TAPE SCOTCH Y434 5.5 MIL ALUMINUM, 2 MIL TYPE 830 RUBBER ADHESIVE

MANF: 3M CO

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006566 1 ■

61568 TAPE SCOTCH Y434 SOUNDDAMP ALUMINUM FOIL GID: DZHDXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.008	0.003		01.50	NONE
A	1	030.0	009.0	0.008	0.003		01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.51	.17	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.27	

85412 TAPE SCOTCH Y435 8 MIL ALUMINUM, 5 MIL TYPE 830 RUBBER ADHESIVE

MANF: 3M CO

....NO TEST DATA AVAILABLE....

85413 TAPE SCOTCH Y436 12 MIL ALUMINUM, 5 MIL TYPE 830 RUBBER ADHESIVE

MANF: 3M CO

....NO TEST DATA AVAILABLE....

69912 TAPE SCOTCH Y9360 GID: DYAKXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.009		0.207	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.54	.01	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	5.9	

62394 TAPE SCOTCH Y9415 POLYESTER ACRYLIC ADHESIVE GID: DZAKCB

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.003	0.003	00.40	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.4E-6	.78	.30	.31	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00017.85	

61019 TAPE SCOTCH Y9460 TRANSFER GID: DYAKXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002	0.003		05.80	SMALL
I	1	030.0	010.4	0.002	0.003	00.34	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.85	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.56	

60596 TAPE SCOTCH Y9469 ACRYLIC TRANSFER GID: DZAKXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.005	0.003	00.00	00.00	NONE
C	1	025.9	014.3	0.005	0.003	00.22	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.29	.02	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00021.52	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006567 3

61018 TAPE SCOTCH Y9473 TRANSFER GID: DZAKXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.009	0.003	00.17	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.23	.01	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.60	

65093 TAPE SCOTCH Y9485 GID: DYXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	030.0	010.0	0.005	0.010	00.00	00.00	NONE
A	1	030.0	010.0	0.005	0.010		01.60	NONE
C	1	030.0	010.0	0.006	0.003	00.20	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.3E-6	2.53	.48	.12	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00021.93	72H-70F-

06531 TAPE SCOTCH Y966 ACRYLIC TRANSFER GID: DZAKXX

MANF: 3M CO SPEC: MB0125-067T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.002	0.003		04.60	NONE
B	2	020.9	014.7	0.003	0.003	00.00	00.00	NONE
B	1	020.9	014.7	0.003	0.003		06.90	NONE
A	1	020.9	014.7	0.003	0.003		01.90	NONE
I	1	024.5	014.5			02.98	12.00	T NONE
A	1	030.0	009.0				01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.68	.53	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00017.55	

61409 TAPE SCOTCH YR364 ALUMINUM GLASS WITH SILICONE ADHESIVE GID: DZFKIA

MANF: 3M CO SPEC: MB0135-062

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	020.9	014.7	0.008			06.50	NONE
I	1	024.5	014.5	0.008		00.74	12.00	T NONE
A	1	025.9	014.3	0.007	0.003		02.20	SMALL
A	1	030.0	010.4	0.007	0.003		02.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	2.21	1.03	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	10.247	

20291 TAPE SCOTCHCAL 30 MYLAR GID: DYXXXX

MANF: 3M CO

....NO TEST DATA AVAILABLE....

06390 TAPE SCOTCHCAL 3623 VINYL ORANGE GID: BPCUXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.44	.41	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.50	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006568 5

06392 TAPE SCOTCHCAL 3627 VINYL GREEN GID: BPCUXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.87	.31	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

00189 TAPE SCOTCHCAL 3650 GID: DYCUXX

MANF: 3M CO

SPEC: MIL-F-8799

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.003		00.00	00.00	NONE
A	1	020.9	014.7	0.003			01.20	NONE
X	2	030.0	010.0	0.003	0.003	0.031	00.10	NONE
X	1	030.0	010.0	0.003	0.003	00.27	06.73	MOD

FSC

RT	FLUID NAME
No test data	

MIL-M-43719T1C1

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.59	.37	.00	

ODOR

RT	RT WEIGHT	CURE
	V 00013.00	

TOXICITY

05616 TAPE SCOTCHCAL 3651 RED GID: DYCUXX

MANF: 3M CO

SPEC: MIL-M-43719T1C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003		04.10	NONE
A	1	030.0	008.0	0.003	0.003		05.60	NONE
A	1	040.0	008.0	0.003	0.003		06.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
X	X 00014.00	

TOXICITY

06391 TAPE SCOTCHCAL 3652 VINYL YELLOW GID: BPCUXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	030.0	010.0	0.003	0.003		00.00	NONE
A	1	030.0	010.0	0.003	0.003	0.5	06.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.30	.56	.00	

ODOR

RT	RT WEIGHT	CURE
X	X 00022.75	

TOXICITY

06394 TAPE SCOTCHCAL 3658 VINYL GRAY GID: BPCUXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.95	2.06	.00	

ODOR

RT	RT WEIGHT	CURE
A	X 19.99	

TOXICITY

64141 TAPE SCOTCHCAL 3930 GID: AKAKXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		020.9	006.2					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	K 00000.33	

TOXICITY

20284 TAPE SCOTCHCAL 530 MYLAR GID: DYCBXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.003	0.003		12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20284 TAPE SCOTCHCAL 530 MYLAR (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	033.0	014.3	0.003	0.003	00.57	12.00	T NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-7	.29	.01		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00011.83	

06398 TAPE SCOTCHCAL 5690 VINYL GID: BPCBXX

MANF: 3M CO SPEC: MCR 7583

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.003	0.003		04.90	MOD
B	2	030.0	009.0	0.003	0.003	00.00	00.00	NONE
B	1	030.0	009.0	0.003	0.003		06.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.48	.09	.00	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
X	00009.72	

63940 TAPE SCOTCHCAL 639 GID: DXXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	030.0	010.0	0.002	0.003	00.34	06.97	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.82	.34	.34	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 00017.80	

69891 TAPE SCOTCHCAL 8010 GREEN TRANSPARENT DYNAMARK GID: CNXXXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 7.55	

69892 TAPE SCOTCHCAL 8014 BLUE TRANSPARENT DYNAMARK GID: CNXXXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 7.58	

60592 TAPE SCOTCHCAL 8015 GID: DYXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.004		00.13	10.40	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.15	.06	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	A 00019.33	

05483 TAPE SCOTCHLITE 3270 VINYL PS GID: DYXXXX

MANF: 3M CO

....NO TEST DATA AVAILABLE....

61479 TAPE SCOTCHLITE 3290 VINYL PS GID: DYCUXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.006	0.003	00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006570 3

61479 TAPE SCOTCHLITE 3290 VINYL PS (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.006	0.003		06.80	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-7	2.52	.29		

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	X 00036.30	

65202 TAPE SCOTCHLITE 680 WITH CTRL TAC GID: DTXXXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	2.23	.95	.14	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	A 00019.18	

06374 TAPE SCOTCHLITE 7610 VINYL P/S GID: DZXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.003		00.70	12.00 T	LARGE
A	1	020.9	014.7	0.003	0.003		03.50	NONE
A	1	025.9	014.3	0.003	0.003		04.80	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.49	3.98	.00	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
	K 00020.87	

65074 TAPE SCOTCHLITE 8850 GID: BPXXXX

MANF: 3M CO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	3.03	1.25	.14	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 00016.60	

06545 TAPE SCOTCHMARK 7883 POLYESTER GID: DYCBX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	025.9	014.3	0.004	0.003		09.90	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.2E-6	1.28	.28	.18	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 00015.98	

63233 TAPE SCOTCHMOUNT 4032 GID: DYCVAK

SPEC: MIL-T-60394A

MANF: 3M CO
R S HUGES COMPANY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.066		00.00	00.00	NONE
I	1	024.5	014.5	0.031	0.003	0.5	12.00	SMALL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.26	.15		24H-90F-0psiaVACUUM

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	A 21.433	

60638 TAPE SCOTCHMOUNT 4408 GID: DYCVAK

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	020.9	014.7	0.110	0.003		00.20	NONE
C	1	020.9	014.7	0.110	0.003	00.30	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006571 5

05601 TAPE SCOTCHSEAL 3655 VINYL BLACK GID: DYCUXX
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.004	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.004	0.003		04.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.65	.38	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00013.35	168H-70F- 24H-150F-

80266 TAPE SHURTAPE PC28F B/L B1255 GID: DYXXXX
MANF: SHUFORD MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	030.0	010.0	0.014	0.003		00.10	NONE
B	1	030.0	010.0	0.014	0.003	0.5	07.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	5.0E-6	4.13	1.30	.86	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	21.229	

63234 TAPE SILICONE MOX/FIBERGLASS GID: DYCKFV
MANF: MOXNESS SPEC: MIL-I-22444

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	145.0	1.000		00.39	12.00	T MOD
I	1	024.5	014.5	0.100		00.19	12.00	T NONE
I	1	025.9	014.3	0.100		00.16	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.4E-6	.73	.24	.05	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00043.94	

20058 TAPE SILICONE SB1050Y/SB1050 GID: DZCKXX
MANF: MOXNESS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.0	014.7	0.050			00.10	NONE
A	1	023.8	014.5	0.050		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62352 TAPE STICK AND STRIP 10470 SILICONE GID: DYCKXX
MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.151	0.003		04.00	NONE
I	1	033.0	014.3	0.150	0.003	00.03	10.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	5.0E-6	1.00	.42		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00019.52	

01730 TAPE STOMASEAL 1522 PS GID: DYXXXX
MANF: 3M CO
....NO TEST DATA AVAILABLE....

60610 TAPE STRETCH RL6000SA GID: DZIADP
MANF: RAYBESTOS-MANHATTAN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.05	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006572 7

62367 TAPE STRETCH SILICONE RUBBER GID: DYDPXX

MANF: MOXNESS SPEC: MIL-I-22444ATSB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.029			02.30	NONE
A	1	020.9	014.7	0.020	0.003		02.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	1.31	.27	.07	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60501 TAPE TA44-2 GID: DYXXXX

MANF: T A MFG CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.009		00.00	00.00	NONE
C	1	023.8	014.5	0.009		00.43	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	9.3E-6	11.06	4.64		

ODOR

RT	RT WEIGHT	CURE
A	V 00017.73	

TOXICITY

61142 TAPE TA88 PS GID: DZXXXX

MANF: T A MFG CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.073			02.40	SMALL
X	1	033.0	014.3	0.073		00.07	06.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.2E-6	2.49	2.88		

ODOR

RT	RT WEIGHT	CURE
A	A 00019.81	

TOXICITY

61516 TAPE TEFLON GID: DYCNXX

MANF: LAKE CITY INDUSTRIAL SPEC: MIL-T-23594 MIL-T-27730A
PERMACEL
W L GORE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.007	0.003		00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	10000	72	70	0.005	0	20
B	PNEU	1500		70	0.004	0	20
X	PNEU	2000		70	0.004	2	09
X	PNEU	2500		70	0.004	1	03
X	PNEU	3000		70	0.004	1	03
B	PNEU	500		70	0.004	0	20
X	PNEU	5000		70	0.004	2	2

65137 TAPE TEFLON FEP GID: DYCNXX

MANF: SHELDAHL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.004	0.003		03.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20252 TAPE TEFLON FEP 4043 AG INCONEL WITH T223 ADHESIVE GID: AKCNMR

MANF: SHELDAHL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.5E-5	1.26	.62		

ODOR

RT	RT WEIGHT	CURE
	A 00020.03	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006573 9

20882 TAPE TEFLON FEP AL/AG Y966 ADHESIVE

MANF: SPEC: MB0125-065T1&2

....NO TEST DATA AVAILABLE....

20880 TAPE TEFLON FEP SILICONE ADHESIVE GID: DYXXXX

MANF: SPEC: MB0125-065T3

....NO TEST DATA AVAILABLE....

20881 TAPE TEFLON FEP WITH Y966 TRANSFER ADHESIVE GID: DYXXXX

MANF: CONN HARD RUBBER SPEC: MB0125-065T3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.004	0.003	00.12	02.70	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.8E-6	.44	.19	.04	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE
No test data		

20285 TAPE TEFLON FLUOROLIN 101 WITH PS SILICONE ADHESIVE GID: DYXXXX

MANF: DE WAL IND

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.006	0.003		02.10	NONE
A	1	033.0	014.3	0.006	0.003		02.30	NONE
X	1	100.0	016.5	0.006	0.003	00.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.6E-7	.53	.32		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00024.55	

61547 TAPE TEFLON PATTERN 2338 GID: DYCNXX

MANF: BALLY RIBBON MILLS SPEC: ST13F074-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.025			04.00	NONE
A	1	030.0	010.0	0.029			04.90	SMALL
A	1	033.0	014.3	0.025			05.80	NONE
X	1	100.0	020.2	0.025		00.90	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.1E-7	.76	.12		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	K 00020.06	

60467 TAPE TEFLON PTFE ANTISEIZE GID: DYCNXX

MANF: LAKE CITY INDUSTRIAL SPEC: MIL-T-277 STM-J-676 MIL-T-27730A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.026	2	19
B	MECH	10000	72	72	0.003	0	21
X	PNEU	12000		72	0.002	3	03
Z	MECH	12000	72	72	0.003	6	06
B	MECH	14.7	72	-297	0.003	0	60
X	PNEU	1500		72	0.002	2	31
X	PNEU	2000		72	0.002	2	02
X	PNEU	2500		72	0.002	2	17
X	PNEU	3000		72	0.002	2	11
B	PNEU	500		70	0.026	0	20
X	PNEU	8000		72	0.002	7	07

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006574 0

65215 TAPE TEFLON THREAD GID: DYCOXX
MANF: LAKE CITY INDUSTRIAL SPEC: MIL-T-27730A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.004	2	20

20763 TAPE TEFLON TY10 SILICONE GID: DYCNCK
MANF: CHEMPLAST SPEC: ST13T1193-1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.025	0.003		04.50	SMALL
A	1	030.0	009.0	0.025	0.003		01.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.2E-6	.39	.16		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.83	

06223 TAPE TEFLON/ACRYLIC 3596 PS GID: DYCNAK
MANF: FRALOCK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	025.9	014.3	0.005	0.003	00.00	00.00	NONE
A	1	025.9	014.3	0.005	0.003		03.80	NONE
A	1	030.0	010.0	0.005	0.003		02.40	SMALL
B	1	033.0	014.3	0.005	0.003		06.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-7	.22	.00	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00026.45	

61574 TAPE TEFLON/ACRYLIC 5396 GID: EBCNAK
MANF: LOCKWOOD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.007	0.010		02.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.4E-6	.22	.01		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00033.67	

64069 TAPE TEFLON/SILICONE GID: DYCNXX
MANF: CONN HARD RUBBER SPEC: MIL-I-23594AT1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.007		00.15	03.27	NONE
A	1	025.9	014.3	0.013	0.003		02.83	NONE
A	1	030.0	010.0	0.007		00.19	02.60	NONE
A	1	030.0	010.0	0.013	0.003		02.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.4E-6	.29	.23	.01	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00021.59	

06028 TAPE TEMP-R-GLASS A2008 GID: EBCNFV
MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.008	0.003		01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.7E-6	.56	.28		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00045.43	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006575 2

06166 TAPE TEMP-R-TAPE C GID: DYFVXX

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003		02.00	NONE
A	1	030.0	010.0	0.004	0.003		01.60	SMALL
A	1	033.0	014.3	0.003	0.003		02.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.31	.16	.28	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00017.06	

62434 TAPE TEMP-R-TAPE G569 GID: DYAKGD

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.008	0.003		05.40	NONE
B	1	024.5	014.5	0.008	0.003	00.30	06.90	NONE
B	1	025.9	014.3	0.008	0.003	00.30	07.90	NONE
A	1	025.9	014.3	0.007	0.003		05.50	NONE
B	1	030.0	010.0	0.007		00.30	07.90	NONE
B	1	030.0	010.0	0.008	0.003	00.30	09.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.0E-6	.63	.09	.14	3H-248F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00021.89	3H-248F-

60667 TAPE TEMP-R-TAPE HM350 TFE/SIL GID: DYCNXX

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
S	1	020.9	014.7	0.003			08.00	NONE
A	1	020.9	014.7	0.007			04.50	NONE
S	1	020.9	014.7	0.008		00.40	12.00 T	NONE
A	1	025.9	014.3	0.005	0.003		02.80	NONE
A	1	030.0	010.0	0.005	0.003		02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.51	.23	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00022.99	

60926 TAPE TEMP-R-TAPE HM430 GID: DZCOAK

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.004	0.003		04.10	NONE
X	2	100.0	020.2	0.004	0.003	00.13	12.00 T	NONE
X	1	100.0	020.2	0.004	0.003	01.91	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.14	.02	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	21.522	

60733 TAPE TEMP-R-TAPE HM50 GID: DYCNXX

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.003		02.50	NONE
A	1	033.0	014.3	0.003	0.003		02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.28	.15	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00022.52	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006576 4

05295 TAPE TEMP-R-TAPE K102R GID: DYAKXX

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.003	0.003		02.20	NONE
A	1	030.0	010.0	0.003			03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.05	.00	.00	3H-248F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00010.33	

05859 TAPE TEMP-R-TAPE K250 GID: DYCDCK

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		02.00	NONE
A	1	030.0	010.0	0.004	0.003		01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	.68	.37	.00	24H-150F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00004.45	

65493 TAPE TEMP-R-TAPE K350SP GID: DYXXXX

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.004			01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	1.50	.48	.71	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00021.55	

63238 TAPE TEMP-R-TAPE ON TEDLAR FILM GID: EBCJXX

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.005			08.50	SMALL
I	1	020.9	014.7	0.009			08.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61786 TAPE TEMP-R-TAPE T155 GID: DZCNCK

MANF: CONN HARD RUBBER

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.4E-6	.32	.16		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

61787 TAPE TEMP-R-TAPE TV350 GID: DZCNCK

MANF: CONN HARD RUBBER

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	024.5	014.5	0.005			00.30	NONE
B	1	024.5	014.5	0.005			08.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.59	.23	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

20497 TAPE TFE GID: DYCNXX

MANF: BALLY RIBBON MILLS SPEC: ST13T132-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.014			01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006577 6

20497 TAPE TFE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	033.0	014.3	0.014			04.30	NONE
X	1	100.0	020.2	0.014		01.67	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.2E-7	.60	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.56	

05087 TAPE TFE/SILICONE 503-5-DC ADHESIVE GID: DZCOXX

MANF: FLUOROCARBON CORP
POLYPENCO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	020.9	014.7	0.022		00.00	00.00	NONE
A	1	020.9	014.7	0.022			00.66	NONE
A	1	030.0	010.0	0.008		00.09	01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.26	.15	.00	24H-149F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00021.55	

05911 TAPE THERMOSEAL TFE TEFLON S12 GID: DYCNXX

MANF: SAUNDERS ENGINEERING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00007.11	

65521 TAPE THERMOSET GID: DYXXXX

MANF: SHELDAHL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.33	.04	.00	3H-210F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

63320 TAPE THREAD SEAL PTFE AQM GID: DYCNXX

MANF: LAKE CITY INDUSTRIAL

SPEC: MIL-T-27730A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	10000	72	70	0.004	0	20
B	PNEU	1500		70	0.004	0	20
X	PNEU	2000		70	0.004	2	09
I	MECH	9000	72	70	0.004	0	05

20356 TAPE TUCK 24 GID: DYXXXX

....NO TEST DATA AVAILABLE....

60722 TAPE VIDEO 400 BLACK GID: BSXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
		023.8	014.5					NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63241 TAPE VIDEO RCA 3M361 GID: DXXXXX

MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.001			06.20	NONE
C	1	023.8	014.5	0.001		04.00	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006578 8

63242 TAPE VIDEO RCA 3M400 GID: DXXXXX

MANF: 3M CO

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	023.8	014.5	0.001			05.20	NONE	No test data	No test data							
X	1	023.8	014.5	0.001		06.00	12.00	T MOD									

61925 TAPE VINYL/COTTON SP252 GID: DZCUFS

MANF: SPECTAPE SPEC: PPP-T-60 T4C1

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	020.9	014.7	0.013	0.003	00.00	00.00	NONE	No test data	No test data							
C	1	020.9	014.7	0.013	0.003	00.98	12.00	T SMALL									

61924 TAPE VINYL/COTTON TUCK 91B GID: DZCUFS

MANF: TUCK INDUSTRIES SPEC: PPP-T-60 T4C1

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	020.9	014.7	0.017	0.003	00.00	00.00	NONE	No test data	No test data							
C	1	020.9	014.7	0.017	0.003	00.48	12.00	T NONE									

65308 TAPE VITON-FLUOREL/CLAMP GID: EXXXXX

MANF: BENDIX SPEC: NLS6E16-XX
MOXNESS

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3				00.75	SMALL	No test data	No test data							

69858 TAPE WHITE WRAPPING (PORTION FROM HYDROCARBON SAMPLE LINE)

MANF: NASA/KSC

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	6.0E-6	1.92	.31	.09		No test data		

60410 TAPE WOVEN GID: DYXXXX

....NO TEST DATA AVAILABLE....

06053 TAPE X389-25-1 BETA GL TEFLON GID: DYHLCN

MANF: DODGE

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.023			01.80	NONE	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.6E-6	.01	.03			No test data		

62053 TAPE/DISPENSER VINYL/PVAC GID: DKCUXX

MANF: 3M CO SPEC: GS-00S-93333

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	023.8	014.5	1.000		00.03	03.80	T MOD	No test data	No test data							
X	1	023.8	014.5	1.000		00.07	03.80	T MOD									

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data						A	A 00025.34	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006579 T

05399 TECFLUORFIL B TFE/11% METAL OX GID: AHCOFW

MANF: THERMECH ENGINEERING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.058		00.00	00.00	NONE

FSC

RT	FLUID NAME
	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	70	0.060	00	20
Z	MECH	1500	72	70	0.060	02	23
B	PNEU	1500		70	0.062	0	20
I	MECH	2000	72	70	0.060	01	08
B	PNEU	2500		70	0.060	0	20
I	MECH	2500	72	70	0.060	01	01
B	MECH	275	72	-297	0.025	0	40
B	PNEU	275		200	0.066	0	180
B	MECH	275	72	200	0.068	0	40
I	MECH	3000	72	70	0.060	01	02
X	PNEU	3000		70	0.060	2	18
X	PNEU	3500		70	0.060	1	05
X	PNEU	4000		70	0.060	1	13
I	PNEU	500		70	0.062	0	05
I	MECH	6000	72	70	0.060	01	02
X	PNEU	7500		70	0.060	1	01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.65	.00		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05367 TECFLUORFIL BF-1TFE/METL OX/GL GID: AHCOFW

....NO TEST DATA AVAILABLE....

05622 TECFLUORFIL RMB1 TFE/CERAM/DYE

....NO TEST DATA AVAILABLE....

05368 TECFLUORFIL TFE/GLASS 105 GID: AHGFCN

....NO TEST DATA AVAILABLE....

05187 TECHFLUORIL TFE/GRAPH CG-11 GID: AHGFCN

MANF: THERMECH ENGINEERING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	70	0.060	0	20
B	PNEU	4500		70	0.078	0	20
X	PNEU	5000		70	0.078	2	07
B	MECH	6000	72	70	0.078	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.31	.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62847 TEFLON 55L2 SEALS GID: CHCDXX

MANF: FLUOROCARBON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-220	0.018	0	20

80164 TEFLON ASBESTOS IMPREGNATED

MANF: SPEC: AMS 3839

....NO TEST DATA AVAILABLE....

62852 TEFLON COATED SLUGS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1500	72	-297	0.065	0	20

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006580 6

63197 TEFLON DEGREASED VACUUM BAKED

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	01329.40	

05502 TEFLON DUROID RT4000 AL GID: BBCNGP

MANF: ROGERS CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.05	.00	.03	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.19	

00649 TEFLON FEP GID: DKBOXX

MANF: AFTON PLASTICS
DUPONT
FLUOROCARBON CORP
THERMECH ENGINEERING

SPEC: MB0130-052 MC284-0389

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.005			03.75	NONE
A	1	030.0	009.0	0.002			04.00	NONE
X	1	030.0	009.0	0.005			03.80	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	-297	0.062	0	6
Z	MECH	1000	72	350	0.062	2	06
Z	MECH	1000	72	350	0.062	2	6
X	PNEU	1000		350	0.064	5	33
X	PNEU	1000		70	0.063	1	16
B	PNEU	1000		70	0.125	0	20
B	MECH	1050	72	-297	0.005	0	0
B	MECH	1050	72	-297	0.010	0	40
X	MECH	1050	10	220	0.070	0	20
X	MECH	1050	10	350	0.059	0	20
X	PNEU	1050		350	0.061	4	10
X	MECH	1050	10	350	0.069	0	20
B	MECH	275	72	-297	0.018	0	20
B	MECH	275	72	150	0.018	0	20
C	MECH	275	20	200	0.098	0	20
I	MECH	3000	72	70	0.125	0	1
I	MECH	4000	72	70	0.125	0	1
B	PNEU	500		70	0.063	0	20
B	MECH	6000	72	70	0.125	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.07	.07	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00024.90	

62848 TEFLON G-83 TFE GID: DMCNXX

MANF: ADEL

SPEC: MIL-P-22241B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.018	0	20

05172 TEFLON PFA 340 FLUORCARBON GID: DKXXXX

....NO TEST DATA AVAILABLE....

06037 TEFLON PFA S160 #10299 GID: DKCNXX

MANF: SAUNDERS ENGINEERING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006581 8

60069 TEFLON PTFE 8573 GID: CHCPXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYZE
	MMH
	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.02	.00	.00	SEE TEST REPORT

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

65177 TEFLON PTFE DISCS GID: DKCOXX

MANF: CONSOLIDATED CONTROLS
FLUOROCARBON CORP
T A MFG CORP

SPEC: 55L2-9 PD-4700187-060

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	10	-297	0.016	1	01

62505 TEFLON PTFE MULTIFILL 427 GID: CACPXX

MANF: GARLOCK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
A	HYD
A	MMH
	N2O4
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

69907 TEFLON PTFE RESIN (POWDERED RAW)

MANF: MMC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.050	00	20

60859 TEFLON RING PISTON RIDER GID: FCXXXX

MANF: AIRCO CRYOGENICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.063	2	21
B	MECH	14.7	72	-297	0.018	0	20
X	PNEU	2000		70	0.063	2	05
X	PNEU	3000		70	0.120	1	01
B	PNEU	500		70	0.120	0	30
B	MECH	6000	72	-297	0.105	0	20

65391 TEFLON SAMPLE GID: COXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297		0	20

62902 TEFLON TFE 3602 GID: DMCOXX

MANF: GULF WANDES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.060	0	20

60375 TEFLON TFE FILLED NOC

MANF: FLOW TECHNOLOGY

MSFC-HDBK-527 REV F 9999942 0006582 T

Information Handling Services, 2000

60375 TEFLON TFE FILLED NOC (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	400	72	-220	0.152	0	20

05576 TEFLON TFE RED STRIPED GID: BNCNXX

MANF: AQM
J & M PRODUCTS

SPEC: MS21122

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.169			01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.3E-6	.05	.02	.01	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00009.52	

00016 TEFLON TFE VIRGIN GID: DKCNXX

MANF: ABSCOA INDUSTRIES
AEROQUIP
AMERICAN HOECHST
AMETEK
AQM
CADILLAC PLASTICS
CALIFORNIA PLASTECK
CARLETON CONTROLS
CHEMPLAST
CIRCLE SEAL
CRANE PACKING CO
DEUTSCH
DIXON INDUSTRIES
DODGE WASMUND
DUPONT
FAIRCHILD
FLUOROCARBON CORP
GSA
GULF WANDES
PARKER HANNIFIN
PORT PLASTICS
RESISTOFLEX CO
SERRA MANUFACTURING
T A MFG CORP
TESCOM CORP
THERMECH ENGINEERING
TRW
U S POLYMERIC

SPEC: AMS 3651
H S 1205 GR A
MIL-I-45208
MIL-P-2224
MIL-P-22241T1
SWM-109
AMS 3651C
MIL-F-8791
MIL-P-19468A
MIL-P-22241
RBO130-097 CF

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.012			02.50	NONE
A	1	025.9	014.3	0.063			00.12	NONE
A	.1	030.0	010.2	0.034			00.71	NONE

FSC

RT	FLUID NAME
A	AMMONIA
A	HYZE
A	MMH
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.060	2	20
A	MECH	1050	72	-297	0.010	0	60
A	MECH	1050	72	70	0.060	0	20
Z	MECH	11500	10	300	0.148	0	20
A	MECH	14.7	72	-297	0.250	0	60
B	PNEU	1500		350	0.010	5	100
X	PNEU	1500		70	0.068	5	92
A	MECH	200	50	-297	0.018	0	20
A	MECH	200	72	-297	0.018	0	20
B	MECH	2000	72	-297	0.060	0	20
X	PNEU	2000		350	0.010	2	16

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006583 1

00016 TEFLON TFE VIRGIN (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID	NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	2000		70	0.068	6	74
B	MECH	2000	72	70	0.070	0	04
B	MECH	2500	72	-297	0.060	2	06
X	PNEU	2500		350	0.010	1	20
X	PNEU	2500		70	0.068	2	04
A	MECH	275	72	-297	0.020	0	20
A	MECH	300	72	150	0.020	0	20
X	PNEU	3000		350	0.010	2	14
X	PNEU	3000		70	0.068	2	13
X	MECH	3300	20	350	0.005	2	31
X	PNEU	3300		350	0.063	19	51
C	MECH	3500	72	-297	0.060	1	01
C	MECH	3500	35	350	0.010	0	40
X	PNEU	3500		350	0.010	02	14
X	PNEU	3500		70	0.060	03	35
Z	MECH	4000	72	-297	0.060	1	01
X	PNEU	4000		70	0.033	2	12
B	PNEU	4000		70	0.060	0	20
B	MECH	4000	72	70	0.060	0	20
X	PNEU	4000		70	0.073	01	01
B	MECH	44	72	400	0.031	0	40
B	MECH	44	72	400	0.249	0	20
B	MECH	45	72	500	0.063	0	200
X	PNEU	4500		70	0.060	2	20
Z	MECH	4500	72	70	0.060	1	32
B	PNEU	500		500	0.063	0	200
Z	MECH	5000	72	70	0.060	2	22
C	MECH	6000	55	70	0.049	0	20
B	MECH	6000	70	72	0.068	0	40
B	MECH	675	72	350	0.069	0	20
B	PNEU	70		500	0.060	0	60
C	MECH	7400	20	70	0.071	0	20
A	MECH	850	72	250	0.069	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.01	.00	.00	
A	6.0E-6	.04	.00	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00067.60	

05548 TEFLON TFE/1% CARBON BLACK GID: DUCNIA

MANF: DUPONT

....NO TEST DATA AVAILABLE....

05501 TEFLON TFE/15% GLASS GID: DUCNIA

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID	NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	4500		77	0.060	2	14

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.12	

05736 TEFLON TFE/15% GRAPHITE GID: FICNGF

MANF: ACCRATRONICS
IMPERIAL ADHESIVE & CHEM INC

SPEC: AMS 3651

Information Handling Services, 2000

05736 TEFLON TFE/15% GRAPHITE (cont)

MANF: ROYAL INDUSTRIES
TESCOM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	1000	72	70	0.103	0	120
B	MECH	15	72	70	0.054	0	80
B	MECH	15	72	70	0.057	0	20
B	MECH	15	72	70	0.064	0	80
B	MECH	50	72	70	0.103	0	20
I	PNEU	6000		200	0.056	0	02
I	PNEU	6000		300	0.056	1	06
I	PNEU	6000		400	0.056	2	03
B	MECH	6000	72	70	0.064	1	50
I	PNEU	6000		73	0.056	0	05
I	PNEU	6000		73	0.056	0	50

05660 TEFLON TFE/25% GLASS GID: DMIACO

MANF: AFTON PLASTICS
AMETEK
CIRCLE SEAL
CROSBY VALVE CORP
FLUOROCARBON CORP
THERMECH ENGINEERING
WHITFORD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		200	0.060	2	100
B	PNEU	1000		220	0.065	0	20
B	PNEU	1000		70	0.060	0	120
B	MECH	1000	72	70	0.061	0	120
C	MECH	1000	72	70	0.095	0	20
B	MECH	1050	72	-297	0.128	0	20
B	PNEU	1050		200	0.160	0	20
X	PNEU	1050		550	0.113	2	07
B	MECH	1050	72	'550	0.117	1	60
B	PNEU	1500		65	0.063	0	20
B	MECH	1500	72	70	0.052	0	20
C	MECH	1500	72	70	0.095	0	20
X	PNEU	1500		70	0.119	2	60
X	PNEU	2000		70	0.059	1	10
X	PNEU	2500		70	0.059	1	21
B	PNEU	3000		65	0.063	0	20
X	PNEU	3500		65	0.063	1	24
X	PNEU	4000		65	0.063	3	24
X	PNEU	4500		65	0.063	4	05
B	PNEU	5000		70	0.095	0	20
X	PNEU	6000		70	0.095	2	06

62506 TEFLON TFE/30% GLASS GID: DMIACO

MANF: FLUOROCARBON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

No test data

FSC

RT	FLUID NAME

No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	44	72	400	0.050	0	20

05326 TEFLON TFE/VACUUM METALIZED AL

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006585 5

61219 TEFZEL ETFE GID: DTCNXX
MANF: DUPONT
FLUOROCARBON CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.060		00.05	01.80	NONE
X	1	030.0	010.0	0.060		00.04	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1000	72	70	0.001	2	27
X	PNEU	1500		70	0.001	1	01
Z	MECH	1500	72	70	0.001	2	02
B	PNEU	500		70	0.001	0	20
Z	MECH	500	72	70	0.001	1	01

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.63	.10	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00021.54	

20555 TEMP SENSITIVE DOTS-PROPRIETAR
MANF: BIG 3
....NO TEST DATA AVAILABLE....

60503 TERMINAL LUG
MANF: SPEC: MIL-T-7928
....NO TEST DATA AVAILABLE....

61147 TERMINAL STRIP 221 PHENOLIC GID: BEBXXX
MANF: BUCHANAN SPEC: MIL-M-14

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.65	2.20	.00	10H-302F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

69921 TETRA-ETCH FLUOROCARBON
MANF: FILISTER
ROGERS CORP
W L GORE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.02	.00	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

20142 TETRALON TF 403-017 GID: XXXXXX
MANF: TETRAFLUOR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	1.500			07.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	3000	72	72	0.040	0	40

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.4E-6	.01	.01		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00002.67	

63253 THERMAL LAG FR MATERIAL GID: DDXXXX
MANF: THERMAL SCIENCES INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.240		00.05	02.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20064 THERMOPLASTIC THERMAL STABILIZ GID: EXXXXX
MANF: VERNAY LABORATORIES
....NO TEST DATA AVAILABLE....

64972 THERMOTROL 2122/MG CONTAINER GID: CACQXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	2.300			00.45	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006586 7 ■

64045 THREAD ARAMID GID: EDXXXX
MANF: SPEC: MIL-T-87128

FLAMMABILITY								FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data		X	MECH	14.7	10	-297	0.020	1	01

06264 THREAD BETA GLASMO TEE
....NO TEST DATA AVAILABLE....

20306 THREAD COTTON 2 CORE GID: EDXXXX
MANF: COATS & CLARK SPEC: V-T-276
....NO TEST DATA AVAILABLE....

60158 THREAD COTTON CORD ALL TYPES GID: EDFSXX
MANF: SPEC: V-T-276
....NO TEST DATA AVAILABLE....

64871 THREAD CRES 300 SERIES
MANF: BRUNSWICK SPEC: SP-AI-0040
....NO TEST DATA AVAILABLE....

61254 THREAD CRES 304 MF-A1 28/61/5Z GID: EDMDXX
MANF: BRUNSWICK SPEC: MB0160-046

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.6E-6	.05	.04			No test data		

64902 THREAD DACRON "B" GID: EDXXXX
MANF: PREMIER

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
B	7.2E-7	.40	.08		72H-70F-	No test data		

60668 THREAD DACRON "E" GID: EDCBXX
MANF: BALLY RIBBON MILLS

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	4.14	1.98	.00		No test data		

64901 THREAD DACRON "FF" GID: EDXXXX
MANF: PREMIER

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	7.2E-6	.85	.33		24H-70F-	No test data		

06602 THREAD GLASS FIBER INORGANIC GID: EDGDXX
MANF: OWENS CORNING SPEC: MB0135-088

THERMAL VACUUM STABILITY						ODOR		TOXICITY
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.2E-6	.23	.08	.07		No test data		

20471 THREAD GLASS PTFE COATED
....NO TEST DATA AVAILABLE....

61863 THREAD GORE-TEX S012T3 PTFE GID: EDCQXX
MANF: W L GORE SPEC: ST15G068

FLAMMABILITY									FSC	OXYGEN COMP						
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.009			00.10	NONE	No test data		No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006587 9

61863 THREAD GORE-TEX S012T3 PTFE (cont.)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.02	.00		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.32	

TOXICITY

20385 THREAD KEVLAR GID: EDJHXX

MANF: SYNTHETIC THREAD — SPEC: ST15K103-01 — ST1SK103-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.008			02.90	NONE
C	2	025.9	014.3	0.020			00.40	NONE
C	1	025.9	014.3	0.020		00.74	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.18	.36	.00	

ODOR

RT	RT WEIGHT	CURE
A	V 00020.09	

TOXICITY

61858 THREAD KEVLAR B132 GID: EDJHXX

MANF: HEMINGWAY BARTLETT — SPEC: ST15K103

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.013			03.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.3E-6	3.39	.09		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.06	

TOXICITY

60841 THREAD KEVLAR B66 GID: EDJHXX

MANF: HEMINGWAY BARTLETT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.009			02.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.7E-6	3.65	.15		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.05	

TOXICITY

64963 THREAD KEVLAR SIZE E GID: EDJHXX

MANF: PREMIER — SPEC: MIL-T-87128

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	7.2E-7	3.93	.15		72H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06465 THREAD NO B8 SIZING 636

....NO TEST DATA AVAILABLE....

20925 THREAD NOMEX GID: EDBVXX

MANF: SYNTHETIC THREAD — SPEC: MIL-C-572TP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.011			00.50	NONE
C	1	025.9	014.3	0.011		00.96	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	6.28	.18	.00	

ODOR

RT	RT WEIGHT	CURE
A	A 00022.39	

TOXICITY

62127 THREAD NOMEX GID: EDBVXX

MANF: SYNTHETIC THREAD — SPEC: MIL-T-43636 — ST15N814-02

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.03	1.81		24H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006588 0

62546' THREAD NOMEX GID: EDBVXX

MANF: SYNTHETIC THREAD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.007			02.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.7E-6	4.00	.07		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

06228 THREAD NOMEX 45/3 ROYAL BLUE GID: EDBVXX

....NO TEST DATA AVAILABLE....

20416 THREAD NOMEX 50/3 TYPE 450 GID: EDBVXX

MANF: ELMORE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.007			03.00	NONE
I	1	033.0	014.3	0.007		02.18	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.38	

69865 THREAD NOMEX E77701/450 ROYAL BLUE SIZE 3/64 GID: EDBVXX

MANF: ELMORE CORP

SPEC: MIL-T-81088T2C2

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	K 19.18	

60914 THREAD NOMEX SILICONE FINISH GID: EDBVCK

MANF: SYNTHETIC THREAD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	1	023.8	014.5	0.007			07.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.7E-6	3.84	.08		

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

20390 THREAD NYLON GID: EDBSXX

MANF: EDDINGTON THREAD

SPEC: MB0135-075
V-T-295

ST15N361

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.005			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.9E-6	3.25	.23	1.97	

ODOR

RT	RT WEIGHT	CURE
A	A 00020.45	

TOXICITY

60161 THREAD NYLON (ALL TYPES) GID: EDBVXX

MANF: EDDINGTON THREAD
SEBRO THREAD CORP

SPEC: ST13N062
ST15N047-01

ST15N047

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002			00.70	NONE
B	2	023.8	014.5	0.010			00.30	NONE
B	1	023.8	014.5	0.010			07.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.35	.01	.00	24H-46F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	V 00020.47	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006589 2

20502 THREAD NYLON E.O.D. COLOR

....NO TEST DATA AVAILABLE....

01596 THREAD NYLON NON-MELTING NOMEX GID: EDBVXX

MANF: EDDINGTON THREAD SPEC: ST15N055-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.012			03.20	NONE
A	1	033.0	014.3	0.012			05.60	SMALL

FSC

RT	FLUID NAME
X	AMMONIA

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.61	.03		

ODOR

RT	RT	WEIGHT	CURE
A	A	00010.04	

TOXICITY

62041 THREAD NYLON SIZE E OLIVE DRAB GID: EDBSXX

MANF: ELMORE CORP SPEC: ST15N871-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.007		01.05	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
V	00000.88		

TOXICITY

20304 THREAD NYLON STRETCH 7 GID: EDBSXX

MANF: SEBRO THREAD CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.030		00.00	00.00	NONE
A	1	033.0	014.3	0.030		00.00	00.00	NONE
A	1	100.0	020.2	0.030			02.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-7	2.34	1.01		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.52	

TOXICITY

20319 THREAD NYLON TCA70143 SIZE B GID: EDBSXX

....NO TEST DATA AVAILABLE....

60455 THREAD NYLON VT295 SIZE E GID: EDBSXX

MANF: EDDINGTON THREAD SPEC: ST15N361-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.012		00.33	12.00	T MOD
X	1	025.9	014.3	0.012		01.17	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.2E-7	3.61	.16		

ODOR

RT	RT	WEIGHT	CURE
A	X	00010.06	

TOXICITY

61492 THREAD PBI FRL-S152 GID: EDHEXX

MANF: FABRIC RESEARCH LAB SPEC: SE-T-0092

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.007			04.50	NONE
A	1	023.8	014.5	0.009			01.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	12.14	.00	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006590 9

61210 THREAD POLYESTER BLACK

....NO TEST DATA AVAILABLE....

20597 THREAD POLYESTER BLACK FF GID: EDCBXX

MANF: HEMINGWAY BARTLETT SPEC: ST15P135-16

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3			00.24	12.00	T MOD
X	1	025.9	014.3			00.75	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.0E-5	2.00	.45		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00008.44	

60268 THREAD POLYESTER F GID: EDCBXX

MANF: SPEC: V-T-285.T1

....NO TEST DATA AVAILABLE....

20595 THREAD POLYESTER GOLD GID: EDCBXX

MANF: HEMINGWAY BARTLETT SPEC: ST15P135-17

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3			00.29	12.00	T NONE
X	1	025.9	014.3			01.97	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.1E-5	.96	.07		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	K 00020.45	

62335 THREAD POLYESTER LOFTEX T16 GID: EDCBXX

MANF: BELDEN SPEC: ST15P1252-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	100.0	020.2	0.004		00.00	00.00	NONE
C	1	100.0	020.2	0.004		07.50	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.2E-6	1.39	.30	.12	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	K 00004.22	

20337 THREAD POLYESTER SIZE E GID: EDCBXX

MANF: HEMINGWAY BARTLETT SPEC: ST14P135-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.010			05.10	SMALL
X	1	033.0	014.3	0.010		01.79	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-7	.60	.26		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.43	

20596 THREAD POLYESTER STEEL SIZE F GID: EDCBXX

MANF: HEMINGWAY BARTLETT SPEC: STP135-18

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3			00.25	12.00	T NONE
X	1	025.9	014.3			01.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS.	TML%	VCM%	RML%	CURE
C	1.0E-5	2.34	.64		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.48	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006591 0

05472 THREAD QUARTZ TFE COATED GID: EDCNHK

MANF: JOHNS-MANVILLE

SPEC: MB0135-029

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.022			02.40	NONE

FSC

RT	FLUID NAME
No test data	

MB0135-072

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.0E-6	.09	.05	.01	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20318 THREAD TEFLON S302 SIZE B GID: EDCNXX

MANF: EDDINGTON THREAD

SPEC: ST13T061-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.008		00.00	00.00	NONE
A	1	033.0	014.3	0.008		00.00	00.00	NONE
A	2	100.0	020.2	0.008			00.30	NONE
A	1	100.0	020.2	0.008			04.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-7	.33	.06		

ODOR

RT	RT WEIGHT	CURE
A	V 00020.04	

TOXICITY

69964 TILE FLEXCO A68 HW

MANF: FLEXCO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	6.09	3.16	.05	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

69969 TILE FLEXCO C10 HW

MANF: FLEXCO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	6.30	3.21	.05	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

69966 TILE FLEXCO SP40 HW

MANF: FLEXCO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	7.57	3.78	.05	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06312 TILE HRSI WITH CC1 AMES COATING

MANF:

SPEC: MA0609-306

....NO TEST DATA AVAILABLE....

05017 TILE REI SILICA 9 GID: FJHKXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.21	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06266 TILE REPAIR TPS1/2/7/21/22

....NO TEST DATA AVAILABLE....

06268 TILE REPAIR TPS11 (INORG)

....NO TEST DATA AVAILABLE....

06402 TILE REPAIR TPS12/16 (INORG)

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006592 2

06403 TILE REPAIR TPS29 (INORG)
....NO TEST DATA AVAILABLE....

06267 TILE REPAIR TPS5 (INORG)
....NO TEST DATA AVAILABLE....

05526 TILE SILICA LI0036/OVERCOATED GID: FJHKXX
MANF: LOCKHEED SPEC: MC364-0006

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.100		00.00	00.00	NONE	No test data		No test data							

05527 TILE SILICA LI0050/OVERCOATED
MANF: LOCKHEED SPEC: MC364-0006

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	1.100		00.00	00.00	NONE	No test data		No test data							

05016 TILE SILICA LI900 GID: FJHKXX

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.25	.00	.00		No test data		

20658 TISSUE DRY AND POLISHING GID: DIXXXX
MANF: C H BEXTER & SONS CO SPEC: ST17P286-01

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
I	6.0E-6	4.53	.03				A 00020.02	

06026 TISSUE DRY MOUNT MT5 GID: DIXXXX
....NO TEST DATA AVAILABLE....

20524 TISSUE TOILET SINGLEFOLD GID: DIXXXX
MANF: CROWN ZELLERBACH SPEC: ST10P804

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data						A	A 00020.10	

06022 TONER HUNT UNIVERSAL 36 GID: APXXXX
....NO TEST DATA AVAILABLE....

06023 TONER XEROX 6500 GID: APGMXX
MANF: XEROX

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data						A	X 00005.35	

60923 TONOMETER INTRAOCULAR PRESSURE GID: FCXXXX
MANF: VARIOUS

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data							A 03565.00	

20671 TOOTHBRUSH ORAL B-40
....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006593 4

20670 TOOTHPASTE CREST
MANF: PROCTER & GAMBLE
....NO TEST DATA AVAILABLE....

80168 TOOTHPASTE NASADENT (NO TUBE)

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	X	21.469	

80264 TOOTHPASTE NASADENT IN TUBE
MANF: SCHERER LABORATORIES

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	X	95.117	

63890 TOWELETTES WASH 'N DRI GID: OIXXXX
MANF: COLGATE-PALMOLIVE

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	X	00008.81	

20602 TOWELS 78% COTTON/22% POLYESTER GID: BFFSCB
MANF: CANNON

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	K	00060.15	

20583 TOWELS KAYDRY PAPER GID: DIXXXX
MANF: KIMBERLY CLARK CORP

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	A	00020.02	

64109 TOYS ASSORTED GID: EXXXXX

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	K	01087.10	

61729 TRANSCEIVER UHF GID: EZXXXX

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	A	03674.20	

64459 TRANSITE GID: DDXXXX
MANF: JOHNS-MANVILLE

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.244		00.00	00.00	NONE	No test data		No test data							

64460 TRANSITE PT401 COATED GID: DDXXXX
MANF: JOHNS-MANVILLE
PROD TECHNIQUES

FLAMMABILITY								FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.262		00.00	00.00	NONE	No test data		No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006594 6

65395 TRUCITE A BLUE GID: DKAJCN
MANF: W S SHAMBAN

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.31	.04	.10	

ODOR

RT	RT WEIGHT	CURE
	X 00022.48	

TOXICITY

05774 TUBING 4100 EPOXY POLYAMINE GID: EFBGXX
MANF: CIBA-GEIGY

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	V 00020.07	

TOXICITY

20101 TUBING ACRYL-A-FA1 FIBERGLASS GID: EGGDXX
MANF: BENTLEY HARRIS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.040			06.30	NONE
C	1	023.8	014.5	0.040		00.39	12.00	T NONE
C	2	030.0	010.0	0.048		00.02	09.00	NONE
C	1	030.0	010.0	0.048		00.18	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.22	.05	.00	24H-302F-

ODOR

RT	RT WEIGHT	CURE
A	A 00020.21	

TOXICITY

06317 TUBING ACRYLIC RIGID GID: DTAKXX
MANF: ROHM & HAAS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.029			08.00	NONE
X	1	025.9	014.3	0.029		00.42	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	K 00018.17	

TOXICITY

60729 TUBING BEN-HAR EXPANDO GID: EFXXXX
MANF: BENTLEY HARRIS SPEC: MB0150-060

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.2E-6	.93	.02		

ODOR

RT	RT WEIGHT	CURE
	K 00021.91	

TOXICITY

06087 TUBING BEN-HAR ST GID: FJFVXX
MANF: BENTLEY HARRIS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.010			00.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.4E-6	.01	.01	.00	24H-150F-

ODOR

RT	RT WEIGHT	CURE
A	A 00020.24	

TOXICITY

65474 TUBING BEN-HAR VITON 44 GID: EFDEXX
MANF: BENTLEY HARRIS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.19	.00	7.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64847 TUBING CEVOLITE X651 GID: EJFOXX
MANF: CELLPACK

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006595 8

64847 TUBING CEVOLITE X651 (cont)

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.100		00.00	00.00	NONE	No test data		No test data							

64859 TUBING DURAPLUS ABS GID: EFAIXX
MANF: ENFIELD INDUSTRY

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	020.9	014.7	0.130			02.90	SMALL	No test data		No test data							
C	1	020.9	014.7	0.130		00.02	12.00	T SMALL										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
X	A 00021.08	

65450 TUBING ECC POLYOLEFIN HS GID: EHCEXX
MANF: 3M CO
SPEC: MIL-I-81765/T

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	1.32	.67	.40	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

65088 TUBING ELEC PTFE HST DUAL WALL GID: EHXXXX
MANF: DIXON INDUSTRIES
SPEC: MIL-I-23053/12 STM 0069-12
STM0069-12

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.040			00.83	NONE	No test data		No test data							
I	1	025.9	014.3	0.040		03.00	12.00	T NONE										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.01	.01	.01	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

06505 TUBING ESTANE GID: EJBYXX
MANF: PLASTIC ENGINEERING
PLASTIC EXTRUSION
SPEC: ST18T1242-02

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.056		00.11	12.00	T MOD	No test data		No test data							
X	1	025.9	014.3	0.056		00.07	12.00	T MOD										
C	2	025.9	014.3	0.050		00.04	12.00	T SMALL										
C	1	025.9	014.3	0.050		00.08	12.00	T SMALL										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.8E-6	1.33	.25	.43	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
A	V 00020.34	

06454 TUBING EVA ETHYLENE VINYL GID: EGCUXX
MANF:
SPEC: ST18T1201-02

FLAMMABILITY									FSC		OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.200			10.70	MOD	No test data		No test data							
X	1	025.9	014.3	0.200		00.10	12.00	T MOD										

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
I	1.3E-6	.28	.00	.05	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
A	A 00019.77	

05053 TUBING FAFTEX PTFE LINER GID: AHCNXX
MANF: FAFNIR BEARING

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006596 T

05053 TUBING FAFTEX PTFE LINER (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	2.0E-6	1.03	.00		

ODOR

RT	RT WEIGHT	CURE
K	00020.28	

TOXICITY

62862 TUBING FEP 100 HST GID: EHBOXX

MANF: PENNTUBE PLASTICS

SPEC: MMS 145 045, MMS 145 092, MMS 145 115, MMS 145 197, MMS 145 290, MMS 145-365, STM 145, MMS 145 060, MMS 145 1.3, MMS 145 180, MMS 145 225, MMS 145-031, MMS 1450440

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	MECH	14.7	72	-297	0.012	0	360

80182 TUBING FEP SPIRAL SPF61 GID: EFXXXX

MANF: JUNKOSHA CO LTD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.040			00.60	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	21.944	

TOXICITY

06494 TUBING FEP TEFLON GID: EFBDCN

MANF: CHEMPLAST

SPEC: MB0130-171

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.011			01.70	SMALL
A	1	025.9	014.3	0.011			02.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.6E-6	.01	.00	.01	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

61569 TUBING FERREX 01-0504 SILICONE GID: CLCKMS

MANF: METEX

SPEC: AMS 3195

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.500			01.00	NONE
I	1	033.0	014.3	0.500		00.02	08.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	00020.02	

TOXICITY

63335 TUBING FIBERGLASS GID: EFFVXX

MANF: AQM
BENTLEY HARRIS

SPEC: MMS 203, STM 203

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	100.0	042.0	0.250		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63139 TUBING FIBERGLASS "S" GID: EFFVXX

MANF: SANTA FE TEXTILES

SPEC: STM 203

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.012		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006597 1

63139 TUBING FIBERGLASS "S" (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	100.0	044.0	0.025		00.00	00.00	NONE

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

06062 TUBING FIBERGLASS S1600-H GID: EFFVXX

MANF: VARFLEX CORP

SPEC: MIL-Y-1140
STM 203

MMS 203

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.015		00.00	00.00	NONE
A	1	100.0	042.0	0.014		00.00	00.00	NONE
A	1	100.0	044.0	0.030		00.00	00.00	NONE
A	1	100.0	044.0	0.011		00.00	00.00	NONE
A	1	100.0	044.0	0.013		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60301 TUBING FIBERGLASS SLV 1200 GID: EFFXXX

MANF: ICO/RALLY CORP

SPEC: MIL-Y-1140
MMS-F-203
STM-F-203

MMS 203
STM 203

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	100.0	043.0	0.075		00.00	00.00	NONE
A	1	100.0	042.0	0.016			00.10	NONE
A	1	100.0	042.0	0.030			02.00	NONE
A	1	100.0	044.0	0.010		00.00	00.00	NONE
A	1	100.0	044.0	0.012		00.00	00.00	NONE
A	1	100.0	044.0	0.014		00.00	00.00	NONE
A	1	100.0	044.0	0.015		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.014	0	40

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.07	.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20113 TUBING FIBERGLASS/ACRYLIC GID: FJFVXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.012			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20110 TUBING FIBERGLASS/EPOXY/PYRE ML COATED GID: EFBGFV

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.023			00.90	NONE
C	1	023.8	014.5	0.023		00.34	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20122 TUBING FIBERGLASS/SILICONE GID: EFFVCK

MANF:

SPEC: MIL-I-18057HA-1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
S	1	023.8	014.5	0.020		00.38		NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61596 TUBING FIBERGLASS/SILICONE 3298-1 GID: EFCKGD

MANF: GENERAL DESIGN INC

SPEC: MIL-I-3190

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.030		00.24	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006598 3

61164 TUBING FLEX PLUROTUBE POLYURETHANE GID: EGCQXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.315			02.30	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.6E-6	1.36	4.17		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.25	

63255 TUBING FLEXAFIT SG2122 GID: EFXXXX

MANF: ESA/ERNO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.115			00.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62168 TUBING FLUOREL 50FC009 GID: EKDEXX

MANF: R E DARLING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.071			05.40	SMALL
X	1	033.0	014.3	0.071			05.80	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00015.16	

65186 TUBING FLUOROELASTOMER HS GID: EHDEXX

MANF: 3M CO/ELECTRICAL DIV

SPEC: MIL-I-23053/13

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.35	.05	.03	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00013.70	

05637 TUBING FP301 INSULTITE HST GID: EFXXXX

MANF: 3M CO/ELECTRICAL DIV

SPEC: AMS 3636-37
MIL-I-23053/5
MIL-I-2305315
MMS-F118

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.022			02.10	NONE
C	1	023.8	014.5	0.022		00.30	12.00	T SMALL
X	1	024.5	014.5	0.015		00.20	12.00	T MOD
X	1	024.5	014.5	0.011		00.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.58	.58	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.85	

20017 TUBING FP301 TYPE 2 POLYOLEFIN HS GID: EHCEXX

MANF: 3M CO/ELECTRICAL DIV
ALPHA WIRE CORP
RAYCHEM CORP
REMTEK CORP

SPEC: AMS 3638
MIL-I-23053/5C2
MIL-I-23053/5
MIL-T-23053/5C2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	019.0	014.3	0.019		00.33	12.00	T MOD
X	2	023.8	014.5	0.011		00.06	12.00	T MOD
X	1	023.8	014.5	0.011		00.20	12.00	T MOD
X	2	023.8	014.5	0.027			00.10	NONE
X	1	023.8	014.5	0.027		00.20	12.00	T MOD
X	1	023.8	014.5	0.014		00.20	12.00	T MOD
X	1	024.5	014.3			00.15	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006599 5

20017 TUBING FP301 TYPE 2 POLYOLEFIN HS (cont)

FLAMMABILITY / FSC / OXYGEN COMP

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	024.5	014.3			00.12	12.00	T MOD										

THERMAL VACUUM STABILITY / ODOR / TOXICITY

RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.7E-6	1.94	.63			A	V	00010.11	

60902 TUBING FRC125 HST GID: EHXXXX

MANF: REMTEK CORP

FLAMMABILITY / FSC / OXYGEN COMP

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	024.5	014.5	0.011		00.20	12.00	T MOD	No test data		No test data							
I	2	025.9	014.3	0.008			01.30	NONE										
X	2	030.0	009.0	0.008		00.03	08.30	MOD										

THERMAL VACUUM STABILITY / ODOR / TOXICITY

RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
X	1.1E-6	3.38	1.49	.29			A	00010.29	

61565 TUBING G10 130C FIBERGLASS/EPOXY GID: COBGIA

MANF: DORCO ELECTRONICS SPEC: MIL-T-25421T1C2

FLAMMABILITY / FSC / OXYGEN COMP

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	2	025.9	014.3	0.075		00.02	12.00	T SMALL	No test data		No test data							
C	1	025.9	014.3	0.075		00.61	12.00	T SMALL										

THERMAL VACUUM STABILITY / ODOR / TOXICITY

RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	9.8E-6	.68	.00			A	A	00020.16	

61088 TUBING GENCOTE 125C GID: EFXXXX

MANF: GENERAL PLASTICS

FLAMMABILITY / FSC / OXYGEN COMP

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.018			01.40	NONE	No test data		No test data							

THERMAL VACUUM STABILITY / ODOR / TOXICITY

RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
I	1.8E-6	.05	.00	.02		No test data			

05926 TUBING GLASS/SILICONE K26-2-305 GID: EFGDCK

MANF: CLAUD S GORDON CO

FLAMMABILITY / FSC / OXYGEN COMP

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7	0.036			11.90	NONE	No test data		No test data							
B	1	023.8	014.5	0.036			06.70	NONE										

THERMAL VACUUM STABILITY / ODOR / TOXICITY

RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
A	2.0E-6	.43	.10				K	00010.05	

65460 TUBING HEAT SHRINKABLE GID: EHXXXX

MANF: SPEC: MIL-I-2212G

THERMAL VACUUM STABILITY / ODOR / TOXICITY

RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT	WEIGHT	CURE
C	1.0E-6	1.70	.54	.00			A	24.20	

69872 TUBING HS HEATRAX 8509 GID: EHXXXX

MANF: ICO/RALLY CORP

FLAMMABILITY / FSC / OXYGEN COMP

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	1	024.5	014.5	0.045		0.08	12.00	T NONE	No test data		No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006600 8

69872 TUBING HS HEATRAX 8509 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	21.84	

61313 TUBING HS RT 1312 VITON GID: EFDEXX

MANF: RAYCHEM CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00020.04	

61595 TUBING HYGRADE SR398 HA1 GID: EDIACK

MANF: MARKEL CORP

SPEC: MIL-I-18057

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.075			00.60	NONE
C	1	023.8	014.5	0.075		00.32	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.54	

20160 TUBING HYGRADE SR398 HB1 GID: EFFVCK

MANF: MARKEL CORP

SPEC: MIL-I-3190 MIL-I-3190TD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.026			03.10	NONE
C	1	023.8	014.5	0.026		00.21	12.00 T	NONE
I	1	025.9	014.3	0.025		00.40	12.00 T	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.2E-7	.54	.18		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00020.25	

80194 TUBING IDEMITSU POLYCARBONATE A2500 GID: EFXXXX

MANF: IDEMITSU OIL CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.125			01.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	22.222	

06107 TUBING INDULITE PS1015 TFE GID: EFXXXX

....NO TEST DATA AVAILABLE....

64968 TUBING INSULTITE KYNAR HST CLEAR NOC GID: EHXXXX

MANF: 3M CO/ELECTRICAL DIV

SPEC: AMS 3632 MIL-I-23053/8

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.009			01.70	SMALL
A	1	030.0	009.0	0.009			01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.5E-6	1.84	.76	.06	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.21	

60637 TUBING INSULTITE VFP876 HST BLACK GID: EHCEXX

MANF: 3M CO/ELECTRICAL DIV

SPEC: AMS 3587 MIL-I-23053/5C3
MIL-R-46846T5

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006601 T

60637 TUBING INSULTITE VFP876 HST BLACK (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.015		00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.97	.69	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.14	

63256 TUBING JUNFLON PFA GID: EFXXXX

MANF: JUNKOSHA CO LTD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.3	0.062			00.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00043.30	

06245 TUBING KEVLAR 49 GID: EGJHXX

MANF: SANTA FE TEXTILES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.127			03.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	3.92	.12	1.74	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
No test data		

61132 TUBING KORVEX FEP HS GID: EIEFXX

MANF: CHEMPLAST

SPEC: MIL-I-23053 MIL-I-23053/12 MIL-I-23053/11

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	100		120	0.055	0	20
B	MECH	100	72	120	0.055	0	20
B	MECH	14.7	72	-297	0.055	0	20
B	MECH	285	72	200	0.008	0	20
B	MECH	45	72	-297	0.007	0	20

61274 TUBING KORVEX TFE HS

MANF: CHEMPLAST

SPEC: MC432-0205 MIL-I-23053/12

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	100	72	-297	0.095	0	20
B	PNEU	1500		70	0.012	0	20
X	PNEU	2000		70	0.012	3	35
B	PNEU	285		200	0.008	0	20
B	MECH	285	72	200	0.008	0	20
X	PNEU	3000		70	0.012	2	11
X	PNEU	4000		70	0.012	1	01
B	PNEU	45		500	0.018	0	20
B	MECH	45	72	500	0.018	0	20
X	PNEU	50		500	0.005	1	20
B	PNEU	50		500	0.090	0	20
X	PNEU	5000		70	0.012	1	01
B	MECH	5500	72	-220	0.004	0	20

65342 TUBING KYNAR 01744-08 SOLDER SLEEVE GID: DWXXX

MANF: RAYCHEM CORP

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006602 1

65342 TUBING KYNAR 01744-08 SOLDER SLEEVE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.56	.14	.00	

ODOR

RT	RT	WEIGHT	CURE
	A	00022.12	

TOXICITY

06621 TUBING KYNAR CONVOLUTED BLACK GID: EFCTXX

MANF: GLENAIR
RAYCHEM CORP

SPEC: MB0150-064T1 STM 0519

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025			00.02	NONE
A	1	020.9	014.7	0.017			00.60	NONE
A	1	024.5	014.3	0.078			00.25	NONE
A	1	025.9	014.3	0.025			01.30	NONE
X	1	030.0	010.4	0.025			08.20	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.9E-6	3.80	1.18	.05	

ODOR

RT	RT	WEIGHT	CURE
X	A	00019.61	

TOXICITY

61575 TUBING KYNAR CONVOLUTED/SS COVR GID: EFCJXX

MANF: ROCKWELL

SPEC: MB0150-064T2B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.016		00.00	00.00	NONE
A	1	030.0	009.0	0.110		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63258 TUBING KYNAR HST/KYNAR BLACK/ALUMINUM GID: EHCTXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5				01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63262 TUBING KYNAR PVF175 HS GID: EHCJXX

MANF: REMTEK CORP

SPEC: MIL-I-23053/8

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	2	025.9	014.3	0.005			00.30	NONE
I	2	030.0	009.0	0.005			00.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.12	.01	.04	

ODOR

RT	RT	WEIGHT	CURE
	A	00006.83	

TOXICITY

65318 TUBING KYNAR PVF2 HST GID: EHCTXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.004			04.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06226 TUBING KYNAR RT1150 CONVOLUTED GID: EGCJXX

MANF: RAYCHEM CORP

SPEC: MB0150-064T1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.014			01.70	SMALL
B	2	025.9	014.3	0.014			00.10	NONE
B	1	025.9	014.3	0.014			07.50	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-7	.66	.10		

ODOR

RT	RT	WEIGHT	CURE
A	K	00019.14	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006603 3

00367 TUBING KYNAR RT850 HST GID: EHCTXX

MANF: RAYCHEM CORP SPEC: AMS 3632 MIL-M-81594T3 MIL-I-23053/8

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.006		00.02	00.60	NONE
X	1	020.9	014.7	0.006		00.07	02.00	MOD
A	1	020.9	014.7	0.015			01.80	NONE
X	1	023.8	014.5	0.005			03.40	MOD
X	1	023.8	014.5	0.005			04.40	MOD
X	1	024.5	014.3	0.008		00.12	12.00	T MOD
X	1	024.5	014.3	0.004		00.11	12.00	T MOD
X	1	024.5	014.3	0.010		00.10	12.00	T NONE
A	1	025.9	014.3	0.011			06.00	SMALL
X	1	025.9	014.3	0.013			03.00	MOD
X	1	025.9	014.3	0.017			06.50	MOD
A	1	030.0	009.0	0.009			05.80	NONE
A	1	030.0	010.0	0.005		00.073	00.42	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.15	.05	.00	

ODOR

RT	RT WEIGHT	CURE
A	A 00021.78	

TOXICITY

69908 TUBING LAMINATED/ROLLED PTFE RESIN/GLASS FABRIC BASE

MANF: AMERICAN DURAFILM SPEC: RB0130-013E T2/CYL#86-1 TO 12 RB0130-013E T2/CYL#86-14 TO 18

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	600	72	-297	0.070	00	20
A	MECH	600	72	-297	0.090	00	280

20391 TUBING LATEX RUBBER GID: EFACXX

MANF: FISHER SCIENTIFIC SPEC: ST15T157-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.119		00.10	12.00	T NONE
X	1	023.8	014.5	0.119		00.15	12.00	T MOD
X	2	025.9	014.3	0.300		00.11	11.90	T MOD
X	1	025.9	014.3	0.300		00.19	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.8E-6	2.80	1.23		60H-70F-

ODOR

RT	RT WEIGHT	CURE
A	A 00020.19	

TOXICITY

06383 TUBING MYLAR HEAT SHRINK GID: EFXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.68	.05	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20035 TUBING NEOPRENE RT510 HST GID: EHDBXX

MANF: RAYCHEM CORP SPEC: MIL-I-23053/1 MIL-R-46846T1C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.020			00.10	NONE
B	1	023.8	014.5	0.020			09.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	7.27	4.45	.00	48H-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006604 5

06606 TUBING NICALON GID: EFXXXX
MANF: DOW CORNING
....NO TEST DATA AVAILABLE....

63430 TUBING NOMEX/TEFLON/SILICONE GID: EFXXXX
MANF: PREECE INC SPEC: MIL-T-24204

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	1	020.9	014.7				06.20	NONE	No test data	No test data							

20006 TUBING NT120 NEOPRENE HST GID: EHDBXX
MANF: REMTEK CORP SPEC: MIL-I-23053/1 MIL-R-46846T2

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	024.5	014.5	0.025		00.04	12.00	T MOD	No test data	No test data							
I	2	025.9	014.3	0.025			00.90	SMALL									

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
C	1.1E-6	1.15	.43	.07			K 00019.76	

62284 TUBING NYLON GID: EIBVXX
MANF: IMPERIAL EASTMAN

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	1	025.9	014.3	0.036		00.14	12.00	T MOD	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data							K 00020.04	

65527 TUBING PLASTIC GID: EHXXXX
MANF: INSULATION SYSTEMS SPEC: MMS-F-144

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data									No test data	B	MECH	14.7	72	-297		00	20

65369 TUBING PLASTIC REINFORCED/CLEAR GID: EIXXXX
MANF: AQM

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.130			12.00	MOD	No test data	No test data							
X	1	025.9	014.3	0.130		00.10	12.00	MOD									

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
No test data						A	V 00042.37	

63202 TUBING POLYCHLOROPRENE HST GID: EFDBXX
MANF: RAYCHEM CORP SPEC: MIL-I-23053/1-1

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	024.5	014.3	0.020			04.00	SMALL	No test data	No test data							

THERMAL VACUUM STABILITY						ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
X	1.0E-6	9.26	2.98	8.80		No test data		

65524 TUBING POLYESTER HST GID: EHXXXX
MANF: AQM

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.007			01.20	NONE	No test data	No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006605 7

65524 TUBING POLYESTER HST (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.007		00.20	12.00	T MOD
X	1	030.0	010.0	0.007		00.20	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.0E-6	.30	.03	.20	

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
A	K	00022.20	

63527 TUBING POLYETHYLENE HST GID: EHCCXX

MANF: ST CLAIR & RUSH

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.043		00.06	01.70	NONE
X	1	025.9	014.3	0.032		00.18	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.71	.33	.00	

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
A	A	00014.60	

20036 TUBING POLYIMIDE ARAMID GID: BFJHXX

MANF: WRIGHT & CO SPEC: MB0135-053

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.025			01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.3E-6	4.05	.32	2.12	

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
No test data			

65330 TUBING POLYOLEFIN B322 HST GID: EFCEXX

MANF: BRADY MFG SPEC: MIL-STD-104B

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	0.020		00.40	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05974 TUBING POLYOLEFIN DUAL WALL HST GID: EHCFXX

MANF: DIXON INDUSTRIES SPEC: MIL-H-83282A MIL-I-23053/4
RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.030		00.06	12.00	T MOD
X	2	023.8	014.5	0.025		00.05	12.00	T MOD
X	1	023.8	014.5	0.025		00.06	12.00	T MOD
X	1	024.5	014.3	0.025		00.20	12.00	T MOD

FSC

RT	FLUID NAME
I	HYD
A	HYZE
A	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	.69	.32		

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	K	00020.10	

60636 TUBING POLYOLEFIN DWP125 GID: EFCEXX

MANF: REMTEK CORP SPEC: MIL-I-23053/4C3

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.025			03.50	MOD
X	2	025.9	014.3	0.025		00.08	12.00	T MOD
X	2	030.0	009.0	0.025		00.08	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.88	.90	1.67	

ODOR

RT

TOXICITY

RT	RT	WEIGHT	CURE
	K	00019.51	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006606 9

06639 TUBING POLYOLEFIN GPF135 HST GID: EHCEXX

MANF: SINCLAIR & RUSH

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
B	1	025.9	014.3			00.30	11.70	SMALL	No test data		No test data						

60609 TUBING POLYOLEFIN GPO135 BLK GID: EFCEXX

MANF: REMTEK CORP SPEC: MIL-I-23053/5C1 MIL-R-46846T5

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	024.5	014.5	0.014			03.20	MOD	No test data		No test data						
X	2	025.9	014.3	0.012			00.50	NONE									
X	2	030.0	009.0	0.012			01.50	NONE									
X	1	030.0	009.0	0.014		00.20	09.50	MOD									

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.1E-6	.69	.05	.20	

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	A	00020.67	

61656 TUBING POLYOLEFIN GPO135 T2

MANF: REMTEK CORP SPEC: MIL-I-23053/5 C2

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	024.5	014.5	0.011		00.30	12.00	T MOD	No test data		No test data						

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.5E-6	.54	.23	.01	

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	K	00007.97	

20019 TUBING POLYOLEFIN GPR135 BLK GID: EFCAXX

MANF: REMTEK CORP SPEC: MIL-I-23053/6

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	2	023.8	014.5	0.012			00.40	NONE	No test data		No test data						
X	1	023.8	014.5	0.012		00.42	11.50	T MOD									
X	1	024.5	014.5	0.016		00.20	12.00	T MOD									
B	2	025.9	014.3	0.017			07.60	SMALL									
I	2	030.0	009.0	0.017		00.04	12.00	T SMALL									

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.13	.28	.00	SEE TEST REPORT

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	K	00019.04	

60300 TUBING POLYOLEFIN HS FLAME RESISTANT GID: EFXXXX

MANF: SPEC: MSFC 276-11XXXX

....NO TEST DATA AVAILABLE....

63254 TUBING POLYOLEFIN HST CLEAR GID: EHCEXX

MANF: NASA/JPL

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	1	024.5	014.5	0.017		00.13	12.00	T MOD	No test data		No test data						

60955 TUBING POLYOLEFIN HST THERMAPOD GID: EHCEXX

MANF: DYNA SYSTEMS SPEC: MIL-I-23053/4C1

FLAMMABILITY									FSC		OXYGEN COMP				
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.001		00.05	11.90	T MOD	No test data		No test data						
X	1	025.9	014.3	0.001		00.09	12.00	T MOD									

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	4.2E-6	.73	.51		

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
	A	00020.59	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006607 0

61543 TUBING POLYOLEFIN RET125 HST GID: EHCEXX

MANF: REMTEK CORP SPEC: MIL-I-23053/4C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.019		00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.1E-6	3.06	2.08	.03	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00019.37	

20022 TUBING POLYOLEFIN RNF100 GID: EHCEXX

MANF: RAYCHEM CORP SPEC: MIL-2305315 MIL-I-23053/5 MIL-I-23053/5C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.010			00.10	NONE
X	1	020.9	014.7	0.010		00.19	12.00	T MOD
X	1	023.8	014.5	0.041			07.70	MOD
X	1	024.5	014.3	0.011		00.25	12.00	T MOD
I	1	025.9	014.3	0.011		00.40	12.00	T NONE
X	2	030.0	010.0	0.015		00.12	12.00	T MOD
X	1	030.0	010.0	0.015		00.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.50	1.74	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
V	00010.28	

06363 TUBING POLYOLEFIN RT102 HST GID: EHCEXX

MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.015			00.80	MOD
X	1	020.9	014.7	0.015		00.17	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20578 TUBING POLYOLEFIN RT1304 HST GID: CHCEXX

MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.069		00.08	07.70	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05887 TUBING POLYOLEFIN RT301 GID: EFCEXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.69	.29	.00	2H-257F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

60844 TUBING POLYOLEFIN RT301/S1024 GID: FJCEXX

MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7				01.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63204 TUBING POLYOLEFIN RT360 TYPE 2 GID: EFCFXX

MANF: RAYCHEM CORP SPEC: MIL-I-23053/6

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.3	0.011		00.16	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00006.20	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006608 2

20021 TUBING POLYOLEFIN RT876 HST GID: EHCFXX

MANF: RAYCHEM CORP

SPEC: MIL-I-23053/5 MIL-R-46846 MIL-R-46846T5C1

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.031			00.10	NONE
X	1	023.8	014.5	0.031		00.14	12.00 T	MOD
X	1	025.9	014.3	0.102			10.50	MOD
X	2	030.0	010.0	0.015			01.60	NONE
X	1	030.0	010.0	0.015		00.30	12.00 T	LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.74	.12	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	10.253	

60635 TUBING POLYOLEFIN RTA125 HST GID: EHCEXX

MANF: REMTEK CORP

SPEC: MIL-I-23053/4C2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.018			04.20	SMALL
X	2	025.9	009.0	0.019			00.40	MOD
X	2	030.0	014.3	0.019			01.80	MOD
X	1	030.0	009.0	0.018		00.10	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.1E-6	1.00	.44	.14	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00020.14	

62328 TUBING POLYOLEFIN TAT125 HST GID: EHCEXX

MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.017		00.11	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63263 TUBING POLYURETHANE CABLE JACKET GID: EFCQXX

MANF:

SPEC: STW3-3134

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.065			04.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20755 TUBING POLYURETHANE NOC GID: EGCQXX

MANF: PLASTIC ENGINEERING

SPEC: ST18T051

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.028			00.30	SMALL
C	1	023.8	014.5	0.028		00.28	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.77	.22	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00019.91	

20427 TUBING POLYVINYLCHLORIDE (PVC) GID: EFHCXX

MANF:

SPEC: MSFC 276-32XXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.062			05.00	MOD
A	1	020.9	014.7	0.094			03.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61612 TUBING POLYVINYLFLOURIDE K46 HS GID: EHCJXX

MANF: RAYCHEM CORP

SPEC: MB0150-059T1

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006609 4

61612 TUBING POLYVINYLFLOURIDE K46 HS (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.005			02.70	SMALL
B	1	025.9	014.3	0.005			10.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.3E-6	.51	.05	.05	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.79	

62860 TUBING PTFE HST GID: EHCOXX

MANF: AMETEK
CHEMPLAST
NORTON
PENNTUBE PLASTICS

SPEC: MIL-I-23053/12
MMS-F-1440078
MMS-F-144
STM-F-144

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.5	0.020		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.095	0	20

62820 TUBING PTFE NON-HEAT SHRINK GID: EFCNXX

MANF: BENTLEY HARRIS
NIHON VALCA
PENNTUBE PLASTICS

SPEC: MIL-I-22129
MMS 2500750
MMS 250313
STM 250
MMS 250
MMS 250250
MMS 250375
STM-F-250

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.014			01.40	SMALL
A	1	024.5	014.5	0.015			01.70	NONE
A	1	024.5	014.5	0.009			02.00	SMALL
A	1	100.0	042.0	0.250			01.30	NONE
X	1	100.0	044.0	0.038		01.20	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	MECH	14.7	72	-297	0.015	0	460

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.01	.00	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00022.22	

62903 TUBING PTFE SHRINKABLE GID: EHCOXX

MANF: AMERICAN MARKETING
DEARBORN WIRE & CABLE
INSULATION MATERIAL
MILLER SALES CO
PENNTUBE PLASTICS
ZEUS INDUSTRIAL

SPEC: MMS-F-144
STM-F-144
MMS-F-1440078

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.004	0	20

05607 TUBING PVF RT1800/1 FLUOROELA GID: EFCJXX

....NO TEST DATA AVAILABLE....

20275 TUBING RAYON GID: EFGOXX

MANF:

SPEC: MIL-I-3190

....NO TEST DATA AVAILABLE....

20158 TUBING RESIN PAPER GRADE 22 GID: DIEFXX

MANF: J L CLARK MFG

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.500		00.01	11.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006610 0

20158 TUBING RESIN PAPER GRADE 22 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	1	023.8	014.5	0.500		00.11	12.00	T SMALL

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00019.94	

65379 TUBING SILASTIC P/N 601405 GID: EIXXXX

MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00010.26	

80296 TUBING SILASTIC P/N VWR62999-405 GID: EFXXXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.062		0.04	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60602 TUBING SILICONE MS50G38 GID: EFCKXX

MANF: MOXNESS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.39	.17	.31	16H-302F-

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

06546 TUBING SILICONE P/N 1665618 GID: EFCKXX

MANF: DOW CORNING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.105			02.50	SMALL
C	1	025.9	014.3	0.105		00.03	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.2E-6	1.01	.27	.04	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
K	00019.76	

60612 TUBING SILICONE RX50 SILASTIC GID: EGCKXX

MANF: DOW CORNING

SPEC: ST18T1241-02 ST29T1839-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.090		00.04	08.00	T MOD
X	2	025.9	014.3	0.084			01.30	MOD
X	1	025.9	014.3	0.084		00.03	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00016.29	

61784 TUBING SILICONE SR200 #18 GID: EGCKXX

MANF: COX & CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5			00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.05	.43	.00	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
A	00008.48	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006611 2

05544 TUBING SILICONE SR200 16 GID: EGCKXX

MANF: COX & CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.032		00.22	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06506 TUBING SOLPRENE 416 GID: EJBYXX

MANF: PLASTIC EXTRUSION

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.061		00.11	12.00	T MOD
X	1	025.9	014.3	0.061		00.23	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.8E-6	.85	.03	:25	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.19	

65473 TUBING SPECIAL FLEX KYNAR K2 GID: EFXXXX

MANF: SUMITOMO

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.10	.03	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

61289 TUBING STM SILICONE NO HST GID: EHCKXX

MANF: INSULATION SYSTEMS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.092			04.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.69	.20		24H-70F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
B	00052.69	24H-150F-

80043 TUBING SUMITUBE POLYOLEFIN HST GID: EHCEXX

MANF: SUMITOMO

SPEC: MIL-I-23053/5

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	024.5	014.5	0.010			00.10	NONE
X	1	024.5	014.5	0.010		00.20	07.70	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.16	.00		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	21.887	

80280 TUBING TEFLON 350 DISPOSAL GID: EFXXXX

MANF: GALTEK CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.625		00.02	00.50	NONE
A	1	025.9	014.3	0.625		00.02	00.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

00578 TUBING TEFLON FEP HST GID: EHBOXX

MANF: QUINTEC INDUSTRIES

SPEC: RB0130-100 CB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.028		00.034	00.60	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	750	72	73	0.030	0	40

62819 TUBING TEFLON FEP HST GID: EHBOXX

MANF: ALPHA WIRE CORP
PENNTUBE PLASTICS

SPEC: MB0150-025C5
MMS 1450031

MIL-I-23053/11
MMS 1450045

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006612 4

62819 TUBING TEFLON FEP HST (cont)

MANF:

SPEC: MMS 1450092, MMS 1450158, MMS 1450225, MMS 145036, MMS 1450500, RB0130-101 CL C, STM 235, MMS 1450141, MMS 1450180, MMS 1450290, MMS 1450365, MMS 1450666, STM 145

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.013		00.00	00.00	NONE

FSC

RT	FLUID NAME
	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1200	184	543	0.034	0	20
A	MECH	14.7	72	-297	0.018	0	360
B	PNEU	50		500	0.125	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.00	.00	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00019.81	

64965 TUBING TEFLON FEP SMT HS GID: EHBOXX

MANF: PENNTUBE PLASTICS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE

No test data

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00049.44	

61407 TUBING TEFLON TFE HST GID: EHCNXX

MANF: CHEMPLAST
PENNTUBE PLASTICS
PENTUBE PLASTICS
SCHAAL ASSOCIATES

SPEC: AMS 3654, MB0150-025C12&3, MMS 1282004, MMS 1282020, MMS 1282205, MMS 1282216, MMS 1282220, MMS 1440003, MMS 1440005, MMS 1440008, MMS 1440010, MMS 1440014, MMS 1440018, MMS 1440022, MMS 144006, MMS 1440125, MMS 1440500, MMS 1441000, STM 144, M1282203, MIL-I-23053/12, MMS 1282016, MMS 1282040, MMS 1282212, MMS 1282218, MMS 144, MMS 1440004, MMS 1440007, MMS 1440009, MMS 1440012, MMS 1440016, MMS 1440020, MMS 1440024, MMS 1440078, MMS 1440250, MMS 1440750, MMS 1441250

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	009.0	0.005			00.10	NONE
A	1	023.8	009.0	0.005			00.10	NONE
A	1	024.5	009.0	0.005			00.10	NONE
A	1	025.9	009.0	0.005			00.10	NONE
A	1	030.0	009.0				00.10	NONE
A	1	030.0	009.0	0.005			00.10	NONE
C	2	100.0	014.7	0.011		00.00	00.00	NONE
C	1	100.0	014.7	0.011		00.39	12.00	T NONE
C	1	100.0	014.5	0.004		00.20	12.00	T NONE

FSC

RT	FLUID NAME
	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	100	72	-297	0.086	0	20
B	PNEU	100		500	0.086	0	20
B	MECH	100	72	500	0.086	0	20
B	MECH	14.7	72	-297	0.080	3	99

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.01	.00	.00	SEE TEST REPORT

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00006.09	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006613 6

63866 TUBING TEFLON TFE ZEUS 14 HST GID: EHCOXX

MANF: DEANCO

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	024.5	014.5	0.125		00.00	00.00	NONE	No test data	No test data							

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
	K 00003.10	

65489 TUBING TEKFIT A222003 HS BLACK GID: EHCEXX

MANF: REMTEK CORP

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	.87	.44	.03	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

02154 TUBING TFE/FEP TYPE WFT GID: EFCNBD

MANF: SPEC: MB0150-025C4

....NO TEST DATA AVAILABLE....

60299 TUBING THERMOFIT 218 HST CONVLEX GID: EHCTXX

MANF: RAYCHEM CORP SPEC: MSFC 276-23XXXX STM0519-020402

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	025.9	014.3	0.032			01.50	SMALL	No test data	No test data							
A	1	030.0	014.3	0.032			00.50	NONE									

65416 TUBING THERMOFIT 222D242 HS GID: EHCEXX

MANF: RAYCHEM CORP

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	.77	.29	.09	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

65417 TUBING THERMOFIT 222D253 HS GID: EHCEXX

MANF: RAYCHEM CORP

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
C	4.0E-6	.74	.27	.09	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
No test data		

63781 TUBING THERMOFIT HS GID: EHXXXX

MANF: RAYCHEM CORP

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
	K 00018.40	

60497 TUBING THERMOFIT RT218 GID: EHCJXX

MANF: RAYCHEM CORP

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7	0.005		00.14	04.00	NONE	No test data	No test data							
X	1	030.0	09.00	0.005		00.06	03.25	MOD									
A	1	25.9	14.3	0.005		00.05	02.75	NONE									

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.26	.00	.00	

ODOR	TOXICITY	
RT	RT WEIGHT	CURE
	A 13.8	

06124 TUBING THERMOFIT S1009 EPOXY GID: EFBGXX

MANF: RAYCHEM CORP

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006614 8

60323 TUBING THERMOFIT S1017 GID: EFXXXX

MANF: RAYCHEM CORP

....NO TEST DATA AVAILABLE....

65319 TUBING THERMOFIT S1044 VITON GID: EFXXXX

MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3			02.20	12.20	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	3.0E-6	2.41	.33	.12	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00014.39	

62552 TUBING THERMOFIT VITON HST GID: EHDEXX

MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.033			01.70	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.6E-6	.08	.02		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00020.27	

80291 TUBING THINWALL P100 SQUARE FORM SPIRAL WRAPPED

MANF: PRECISION TUBE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.025		0.12	11.80	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61926 TUBING TYGON B44-3 GID: EGBYXX

MANF: NORTON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	32.91	99.90		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05425 TUBING TYGON PVC GID: EFHCXX

....NO TEST DATA AVAILABLE....

05960 TUBING TYGON R3603 GID: EFXXXX

....NO TEST DATA AVAILABLE....

60601 TUBING TYGON S54HL GID: EFXXXX

MANF: NORTON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.030		00.20	09.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	22.00	11.88	.03	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.19	

64840 TUBING TYGON/L-T-80 TAPE WRAP GID: DZCKFK

MANF: LAMART CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3			00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

64817 TUBING VACUFLEX PVC HST GID: EGHCXX

MANF: FLEXIBLE TUBING

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006615 T ■

64817 TUBING VACUFLEX PVC HST (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.225			08.00	MOD
X	1	020.9	014.7	0.200			10.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06234 TUBING VARGLASS 81600H GID: BPFVCK
MANF: VARFLEX CORP
....NO TEST DATA AVAILABLE....

05634 TUBING VARGLASS H/HO NON-FRAY GID: FJGDXX
MANF: VARFLEX CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.009			00.50	NONE
A	1	023.8	014.5	0.014			00.80	NONE
A	1	023.8	014.5	0.013			00.60	NONE
A	1	023.8	014.5	0.012			00.10	NONE
A	1	025.9	014.3	0.016		00.00	00.00	NONE
A	1	030.0	010.0	0.014		00.00	00.00	NONE
A	1	033.0	014.3	0.016		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	3.7E-6	.03	.00		24H-150F-

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.18	

TOXICITY

65476 TUBING VARGLASS VITON 231 GID: EFDEXX
MANF: VARFLEX CORP

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.04	.00	.02	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

62855 TUBING VIRGIN FEP TEFLON GID: EFCNXX
MANF: CREAVEY SEAL CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	14.7	72	-297		1	20

05202 TUBING VITON HST GID: DODEXX
MANF: 3M CO/ELECTRICAL DIV
ECC PRODUCTS
RAYCHEM CORP
SPEC: P/N 8600750

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.140			00.10	NONE
A	1	024.5	014.5	0.033			00.70	SMALL
A	1	025.9	014.3	0.040		0.02	01.00	NONE
A	1	030.0	009.0	0.033			01.30	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.5E-6	.88	.08	.04	

ODOR

RT	RT	WEIGHT	CURE
	K	29.80	

TOXICITY

05759 TUBING VITON RT1146 HST GID: EHDEXX
MANF: RAYCHEM CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.021			00.10	SMALL
A	1	025.9	014.3	0.015		0.03	02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006616 1

05759 TUBING VITON RT1146 HST (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.016		0.07	12.00	SMALL
A	1	025.9	014.3	0.016		0.07	03.25	NONE
A	1	030.0	009.0	0.016		00.03	02.25	NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.37	.07	.00	

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.17	

20135 TUBING VITON V138A GID: FJDFXX

MANF: NICHOLS ENGINEERING

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.065			00.20	SMALL
A	1	025.0	014.5	0.065			00.20	SMALL
A	1	030.0	014.5	0.065			00.10	SMALL
A	1	035.0	014.5	0.065			00.70	SMALL
X	1	040.0	014.5	0.064		00.06	08.00	T MOD
I	1	045.0	014.5	0.065		00.07	08.00	T SMALL
X	1	050.0	014.5	0.066		00.05	07.00	T MOD

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	5.0E-7	.37	.00		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.00	

62464 TUFFAK POLYCARBONATE F1 GID: DUCAXX

MANF: ROHM & HAAS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	023.8	014.5	0.005		0.120	01.40	MOD

THERMAL VACUUM STABILITY

No test data

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00224.57	

80159 TUNGSTEN CARBIDE

....NO TEST DATA AVAILABLE....

80160 TUNGSTEN CARBIDE AFBMA GRADE 25

....NO TEST DATA AVAILABLE....

80161 TUNGSTEN CARBIDE CARBOLOX GRADE 44

....NO TEST DATA AVAILABLE....

80163 TUNGSTEN CARBIDE K-96

....NO TEST DATA AVAILABLE....

80162 TUNGSTEN CARBIDE KENNAMETAL 601

....NO TEST DATA AVAILABLE....

05043 TURCON/TFE

....NO TEST DATA AVAILABLE....

65366 ULTRA ETHYLUX POLYETHYLENE GID: DUCCXX

MANF: WESTLAKE PLASTICS CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	1.000			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006617 3

65366 ULTRA ETHYLUX POLYETHYLENE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	030.0	010.0	1.000			03.90	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00022.61	

61187 VACUUM CLEANER HANDIVAC II GID: FCXXXX

MANF: HOOVER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3			00.08	08.60 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	02566.16	

61190 VALVE NON-REBREATHER GID: FCXXXX

MANF: SIERRA ENGINEERING SPEC: SV778533-1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00036.26	

61791 VALVE OXYGEN CHECK GID: FEXXXX

MANF: CARLETON CONTROLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	1500		70		0	20

61780 VALVE SUPERIOR 430 GID: FEBSXX

MANF: SUPERIOR VALVE CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	PNEU	3000		70		0	60

20262 VARNISH BC354 CLEAR HI-TEMP GID: ASXXXX

....NO TEST DATA AVAILABLE....

80253 VARNISH DAISO DAP TYPE A GID: AKXXXX

MANF: OSAKA SODA CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	030.0	010.0	0.016	0.010	00.09	12.00	NONE
C	1	030.0	010.0	0.016	0.010	1.1	12.00	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	3.0E-6	20.60	.08	.16	24H-70F- 1H-300F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	8.568	24H-70F- 1H-302F-

05468 VARNISH DORYL DIPHENYL OXIDE GID: ATEDXX

MANF: WESTINGHOUSE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.002	0.003		00.90	NONE
I	1	025.9	014.3	0.005	0.003	0.42	12.00 T	SMALL
A	1	030.0	009.0	0.005			02.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
B	00008.61	12.5H-347F-

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006618 5

20185 VARNISH GLYPTAL 1202 ALK GID: ATAOXX
MANF: GENERAL ELECTRIC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.55	2.46	.00	4H-257F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00009.54	SEE MFG

05669 VARNISH GLYPTAL RED CAT 90-2 GID: ASXXXX
....NO TEST DATA AVAILABLE....

06017 VARNISH IMPREGNATING SR224 SILICONE
....NO TEST DATA AVAILABLE....

80038 VARNISH IMPREGNATION IMIDALLOY TVB 2705 GID: ASXXXX
MANF: TOSHIBA

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	024.5	014.5	0.017	0.003	0.5	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	18.978	

20248 VARNISH INSULATING U86F
MANF: INSL-X PRODUCTS CORP
....NO TEST DATA AVAILABLE....

05715 VARNISH INSULON 100 EPOXY GID: AKBGXX
MANF: PETERSON CHEMICAL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	2	023.8	014.5	0.005	0.003	00.00	00.00	NONE
A	1	023.8	014.5	0.005	0.003		01.90	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	00010.15	24H-150F-

06457 VARNISH INTUMESCENT R66 FR
....NO TEST DATA AVAILABLE....

05482 VARNISH NYLON 7-11 GID: AKBSXX
MANF: NYCOTE LABORATORIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.001	0.003		01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

05216 VARNISH PHENOLIC ELECTRIC INSULATION GID: APXXXX
SPEC: MIL-I-24092
MANF:
....NO TEST DATA AVAILABLE....

20256 VARNISH PHENOLIC M4068 CLEAR GID: ASBXXX
....NO TEST DATA AVAILABLE....

05375 VARNISH SILICONE DC997 GID: AKCKXX
SPEC: MIL-I-24092C200
MANF: DOW CORNING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.6E-7	.71	.27		24.5H-70F- 4H-350F-

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006619 7

06434 VARNISH SR80 SILICONE GID: ASXXXX
MANF: GENERAL ELECTRIC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.003	0.003		00.70	NONE
A	1	030.0	009.0	0.003	0.003	00.00	00.00	NONE
A	1	100.0	020.2	0.003	0.003		02.10	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.6E-6	6.73	1.41	.04	24H-70F- 24H-150F-

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
B	00012.59	24H-70F- 24H-150F-

20205 VARNISH SYNTHITE AC29-76 GID: ALBXXX
MANF: JOHN C DOLPH CO SPEC: MIL-V-173

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.001	0.003		04.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00004.46	24H-70F-

20024 VARNISH SYNTHITE AC41 CLF GID: ALBXXX
MANF: DOLPH CHEMICAL
....NO TEST DATA AVAILABLE....

61809 VELOSTAT 1810 SERIES GID: DTCFFO
MANF: 3M CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	020.9	014.7	0.024		00.05	11.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60136 VELOSTAT 2.5 MIL
MANF: CUSTOM MATERIALS INC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.67	.21	.00	

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

06378 VESPEL KS105 GID: DPCDXX
MANF: DUPONT SPEC: ST95V939-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.500		00.01	04.50	SMALL
A	1	030.0	009.0	0.500		00.01	00.90	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	MECH	1500	20	70	0.059	0	1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.35	.00	.00	SEE TEST REPORT

ODOR

RT
No test data

TOXICITY

RT	RT WEIGHT	CURE

68670 VESPEL SP-22
MANF: DUPONT
....NO TEST DATA AVAILABLE....

05123 VESPEL SP1/POLYIMIDE GID: DMCDGF
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		200	.060	03	227
X	PNEU	1000		200	0.060	3	227

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006620 3

05123 VESPEL SP1/POLYIMIDE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		250	.042	02	07
X	PNEU	1000		250	0.042	2	07
Z	MECH	1000	10	250	0.055	2	9
B	PNEU	1000		70	0.042	0	20
B	PNEU	1000		70	0.042	00	20
Z	MECH	1000	72	70	0.050	3	16
C	MECH	1050	40	70	0.070	1	20
Z	MECH	1050	30	70	0.070	1	06
C	MECH	1050	30	72	0.060	0	20
X	PNEU	1250		70	.041	02	33
X	PNEU	1250		70	0.041	2	33
X	PNEU	1500		70	.041	01	20
I	PNEU	1500		70	0.041	1	20
Z	MECH	1500	72	70	0.050	2	2
B	MECH	200	72	70	0.059	0	20
X	PNEU	2000		70	.041	02	02
X	PNEU	2000		70	0.041	02	02
Z	MECH	2500	72	70	0.059	1	1
Z	MECH	265	72	70	0.059	2	6
B	MECH	300	72	-297	0.057	0	20
X	MECH	3300	10	200	0.058	0	20
X	MECH	3300	20	250	0.037	0	20
X	PNEU	3500		70	.053	01	07
I	PNEU	3500		70	0.053	1	07
Z	MECH	400	72	70	0.060	4	9
Z	MECH	4000	72	66	0.050	1	2
B	PNEU	500		250	0.042	0	20
B	PNEU	500		250	0.042	00	20
Z	MECH	500	72	70	0.050	2	7
X	MECH	5500	20	70	0.050	0	20
B	PNEU	600		250	0.059	0	20
B	PNEU	600		250	0.059	00	20
X	PNEU	600		250	0.060	02	213
X	PNEU	600		250	0.060	2	213
X	MECH	600	10	250	0.060	0	200
X	MECH	600	10	500	0.051	1	60

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.53	.01	.96	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05122 VESPEL SP21 GID: DMCDGF

MANF: DUPONT
FLUID MECHANICS VALVE CO

SPEC: AND 63503
MB0130-140
MB0130-142T1-11
MC276-0010
MC284-0395
MC284-0397
AND 64927
MB0130-142
MC276-0004
MC276-0012
MC284-0396

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.123		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	100	72	-297	0.053	0	20
X	PNEU	1000		200	0.060	01	58
B	PNEU	1000		70	0.060	00	160
X	PNEU	10000		70	0.060	1	8
Z	MECH	10000	72	70	0.060	1	16

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006621 5 ■

05122 VESPEL SP21 (cont)

FLAMMABILITY									FSC	
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME

OXYGEN COMP							
RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
C	MECH	1050	55	-297	0.060	0	20
B	MECH	14.7	72	-297	0.060	0	20
X	PNEU	1500		200	0.060	08	59
B	PNEU	1500		70	0.057	00	20
C	MECH	1500	72	70	0.060	01	09
C	MECH	2000	72	70	0.060	00	20
B	PNEU	2000		70	0.075	00	23
B	MECH	250	72	70	0.060	0	20
B	PNEU	2500		70	0.050	00	20
Z	MECH	2500	35	70	0.060	01	09
X	PNEU	2500		70	0.075	02	60
C	MECH	275	55	-297	0.040	02	33
C	MECH	275	72	200	0.028	04	82
C	MECH	275	40	200	0.060	0	20
B	PNEU	275		350	0.058	00	124
C	MECH	275	35	350	0.059	00	20
C	MECH	275	30	350	0.060	0	20
X	PNEU	3000		70	0.050	02	22
C	MECH	3000	55	70	0.060	0	20
X	PNEU	3000		70	0.075	01	07
X	PNEU	3300		150	0.060	06	60
X	PNEU	3300		150	0.060	6	60
C	MECH	3300	35	210	0.060	0	20
Z	MECH	3500	72	70	0.060	02	22
X	PNEU	3500		70	0.075	01	12
Z	MECH	400	72	-220	0.150	03	03
B	PNEU	400		200	0.060	00	180
X	PNEU	4000		70	0.061	02	24
X	PNEU	4000		70	0.075	02	03
X	PNEU	4000		70	0.125	01	24
B	PNEU	4500		70	0.050	0	20
B	PNEU	4500		70	0.050	00	20
Z	MECH	4500	72	70	0.060	01	03
B	PNEU	4500		70	0.075	02	20
X	PNEU	4500		70	0.125	02	04
X	PNEU	500		200	0.060	02	38
X	PNEU	5000		70	0.050	02	04
Z	MECH	5000	72	70	0.060	01	02
X	PNEU	5000		70	0.075	03	24
X	PNEU	5000		70	0.125	02	21
X	PNEU	5500		70	0.075	02	25
C	MECH	600	50	250	0.038	00	20
C	MECH	600	40	250	0.060	0	20
X	PNEU	6000		70	0.060	02	10
X	PNEU	6000		70	0.075	02	06
X	PNEU	6000		70	0.125	02	18
B	PNEU	7500		70	0.061	00	20
B	PNEU	7500		70	0.125	02	18
X	PNEU	8000		70	0.061	02	26
Z	MECH	9000	72	70	0.060	01	20
Z	MECH	9500	72	70	0.060	1	15
X	PNEU	9500		70	0.061	1	12

THERMAL VACUUM STABILITY					
RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.52	.01	.00	

ODOR	TOXICITY		
RT	RT	WEIGHT	CURE
A	K	00021.46	

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006622 7 ■

05182 VESPEL SP211 POLYIMIDE/GRAPHITE/TFE GID: AHCDCO

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1000	72	70	0.061	1	02
B	MECH	14.7	72	-297	0.060	0	40
X	MECH	220	10	250	0.060	0	20
B	MECH	280	72	250	0.058	0	40
B	PNEU	280		250	0.059	0	140
X	MECH	850	I0	10	0.050	0	20
Z	MECH	8800	36	-220	0.015	03	03

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.48	.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06086 VESPEL SP22 POLYIMIDE/40% GRAPHITE

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.251		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.58	.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05057 VESPEL SP3 GID: DKCDGF

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
Z	MECH	1000	72	70	0.068	02	02
C	MECH	14.7	45	-297	0.068	0	20
B	PNEU	1500		70	0.061	0	20
X	MECH	1500	72	70	0.068	01	01
Z	MECH	1500	72	70	0.125	3	20
X	PNEU	2000		70	0.061	1	20
Z	MECH	500	72	70	0.068	02	04

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.17	.00	.64	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05304 VESPEL SP31/SP3 POLYIMIDE/MOS2 GID: DKCDEJ

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.54	.01	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05379 VESPEL SP5 POLYIMIDE/GLASS GID: CHCDIA

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.065			00.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	PNEU	1000		70	0.062	4	65
X	PNEU	1500		70	0.062	4	24
X	PNEU	2000		70	0.062	3	08
X	PNEU	2500		70	0.062	1	01
X	PNEU	3000		70	0.062	1	02
X	PNEU	4000		70	0.062	1	01
B	PNEU	500		70	0.062	0	80

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.49	.01	.00	

ODOR

RT	RT WEIGHT	CURE
A	V 00020.42	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006623 9

63754 VESTIBULAR EXPERIMENT BRS GID: EXXXXX
MANF: M I T CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	05276.00	

TOXICITY

63752 VESTIBULAR EXPERIMENT DOME STOWAGE GID: EXXXXX
MANF: M I T CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	07827.00	

TOXICITY

63753 VESTIBULAR EXPERIMENT MICROCOMPUTER GID: EXXXXX
MANF: M I T CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	18331.00	

TOXICITY

63750 VESTIBULAR EXPERIMENT MIDDECK TRAY GID: EXXXXX
MANF: M I T CHEMICAL

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	02631.00	

TOXICITY

61264 VYDAX 1000
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	10000	72	130	0.050	1	20
B	PNEU	2500		70	0.050	0	20
X	PNEU	3000		70	0.050	1	20
B	PNEU	3500		70	0.050	0	20
X	PNEU	4000		70	0.050	2	20
B	MECH	5000	72	130	0.050	0	2
X	PNEU	5000		70	0.050	2	15
B	MECH	6000	72	130	0.050	0	2
X	PNEU	6000		70	0.050	2	07
X	PNEU	7000		70	0.050	1	01
B	MECH	8500	72	130	0.050	0	20
B	MECH	9000	72	130	0.050	1	20
B	MECH	9500	72	130	0.050	1	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.67	.08		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

62112 VYDAX AR FLUOROCARBON GID: AXEFXX
MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.002	0.003		01.20	NONE
A	1	033.0	014.3	0.002	0.003		01.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	515	72	-260	0.020	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	X	00009.46	

TOXICITY

65033 WALLBOARD/PASTE/SEAMING TAPE GID: EXXXXX
MANF: AQM

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006624 0 ■

65033 WALLBOARD/PASTE/SEAMING TAPE (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
X	HYZE
X	MMH
X	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65034 WALLBOARD/PASTE/TAPE COATED GID: EXXXXX

MANF: AQM

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
X	HYZE
X	MMH
X	N2O4

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62474 WARMER FOOD NEMA G-11 EPOXY/GL GID: EXBGHN

MANF: COMMERCIAL PLASTICS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.117			00.50	SMALL
A	1	033.0	014.3	0.117			00.80	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00010.25	

62544 WASH CLOTHS BABY UNSCENTED GID: BFXXXX

MANF: JOHNSON & JOHNSON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00191.60	

20771 WAX ENTEK 18 WATER BASE

....NO TEST DATA AVAILABLE....

20220 WAX ETHONE 18

MANF: AMER SMELTING & RF

....NO TEST DATA AVAILABLE....

80087 WAX ORIGINAL PLEDGE AEROSOL

MANF: JOHNSON & JOHNSON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
X	0.087	24H-70F-

69899 WEBBING 22DPT-H GID: BMXXXX

MANF: GUDEBROD BROS SILK

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	024.5	014.5	0.010			04.40	LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	22.22	

64916 WEBBING 3600 COND. R GID: BMBSXX

MANF: SPEC: MIL-W-40880

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.054		00.13	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006625 2

64916 WEBBING 3600 COND. R (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.2E-6	3.47	1.03		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60101 WEBBING COTTON ALL TYPES

....NO TEST DATA AVAILABLE....

00468 WEBBING DACRON GID: BMCBXX

MANF: PHOENIX TRIMMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	6.0E-7	.28	.01		144H-120F-0psia1E-6 TORR

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64903 WEBBING DACRON GID: BMCBXX

MANF: BALLY RIBBON MILLS

SPEC: MIL-W-56256

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	4.4E-6	.41	.07		60H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62151 WEBBING DACRON 1250LB GID: BMCBXX

MANF: BALLY RIBBON MILLS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.56	.18		24H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20289 WEBBING DACRON 1287 GID: BMCBXX

MANF: BALLY RIBBON MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	
A	1	020.0	010.5	0.064			03.75		NONE
I	1	025.0	010.5	0.070		00.13	12.00	T	NONE
X	2	025.9	014.3	0.062		00.07	12.00	T	MOD
X	1	025.9	014.3	0.062		00.16	12.00	T	MOD
X	1	025.9	014.3	0.064		00.16	12.00	T	MOD
X	1	030.0	010.5	0.062		00.21	12.00	T	MOD
X	1	035.0	010.5	0.063		00.13	12.00	T	MOD
X	1	050.0	010.5	0.063		00.41	12.00	T	MOD
X	1	100.0	016.5	0.064		01.01	12.00	T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-7	.25	.03		

ODOR

RT	RT WEIGHT	CURE
A	A 00025.52	

TOXICITY

61265 WEBBING DACRON 1695 GID: BMCBXX

MANF: BALLY RIBBON MILLS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	8.9E-7	.30	.01		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64505 WEBBING DACRON 2300 LB GID: BMCBXX

MANF: BALLY RIBBON MILLS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	7.2E-7	.14	.00		24H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64908 WEBBING DACRON 280 GID: BMCBXX

MANF: BALLY RIBBON MILLS

MSFC-HDBK-527 REV F 9999942 0006626 4

Information Handling Services, 2000

64908 WEBBING DACRON 280 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.9E-7	.51	.10		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

62152 WEBBING DACRON 300LB GID: BMCBXX
MANF: BALLY RIBBON MILLS SPEC: EI-4183

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	7.2E-7	.26	.09		24H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64907 WEBBING DACRON 600 LB GID: BMCBXX
MANF: BALLY RIBBON MILLS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	6.0E-7	.32	.03		24H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64906 WEBBING DACRON 80 LB GID: BMCBXX
MANF: BALLY RIBBON MILLS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	7.2E-7	.47	.08		24H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

60472 WEBBING DACRON 800 LB GID: BMCBXX
MANF: BALLY RIBBON MILLS SPEC: III 144301-TY5

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.0E-7	1.09	.66		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64904 WEBBING DACRON 900 LB GID: BMCBXX
MANF: BALLY RIBBON MILLS SPEC: III 114000-T2

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	7.9E-7	.42	.06		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

06254 WEBBING ELASTIC 1707 GID: BMXXXX
MANF: GEORGE C MOORE CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	020.9	014.7	0.052			00.50	MOD
X	1	020.9	014.7	0.052		00.14	12.00	T MOD
X	2	025.9	014.3	0.050			09.10	MOD
X	1	025.9	014.3	0.053		00.36	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	7.2E-7	1.11	.30		

ODOR

RT	RT WEIGHT	CURE
A	V 00020.01	

TOXICITY

03323 WEBBING FLUOREL GLASS RL 3603 GID: BMIADE
MANF: RAYBESTOS-MANHATTAN

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.050			01.20	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	K 00046.37	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006627 6

61110 WEBBING KEVLAR 1000 LB GID: BMJHXX
MANF: BALLY RIBBON MILLS — SPEC: MIL-T-87130T6C4 — SS-323242T5C8

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.16	.16		

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64921 WEBBING KEVLAR 10000 LB GID: BMJHXX
MANF: BALLY RIBBON MILLS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.9E-7	1.74	.14		100H-275F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20315 WEBBING KEVLAR 1758 GID: BMJHXX
MANF: BALLY RIBBON MILLS — SPEC: ST13W042-03

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.025			05.00	NONE
C	1	033.0	014.3	0.025		00.19	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	7.1E-7	3.13	.14		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.05	

TOXICITY

63245 WEBBING KEVLAR 1813-2 GID: BMJHXX
MANF: BALLY RIBBON MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.050		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
	X 00057.40	

TOXICITY

64920 WEBBING KEVLAR 550 LB GID: BMJHXX
MANF: BALLY RIBBON MILLS — SPEC: MIL-T-87130T1C2

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-7	2.85	.02		24H-70F-

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

64918 WEBBING KEVLAR 6000 LB GID: BMJHXX
MANF: BALLY RIBBON MILLS — SPEC: MIL-T-87130T6C9

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	6.0E-6	1.99	.04		24H-275F-0psia3E-6 24H-70F-0psia3E-6

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

20381 WEBBING KEVLAR FRL-S-196 GID: BMXXXX
MANF: FABRIC RESEARCH LAB — SPEC: ST13K101-03

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.025			01.80	NONE
B	1	033.0	014.3	0.025			08.80	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.04	.07		

ODOR

RT	RT WEIGHT	CURE
A	A 00020.11	

TOXICITY

60793 WEBBING KEVLAR FRL-S201 GID: BMJHXX
MANF: FABRIC RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.036			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006628 8

60793 WEBBING KEVLAR FRL-S201 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.8	014.3	0.034			02.80	NONE
I	1	033.2	015.5	0.040		00.12	09.70	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	4.0E-6	3.28	.26		

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00010.07	

06316 WEBBING MURDOCK X854 POLYESTER GID: BMCBXX

MANF: AMI INDUSTRIES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.086		00.05	12.00	T MOD
X	1	025.9	014.3	0.086		00.19	12.00	T MOD

THERMAL VACUUM STABILITY

No test data

FSC

No test data

OXYGEN COMP

No test data

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	K 00019.96	

20372 WEBBING NEOTEX 12 GID: BMXXXX

....NO TEST DATA AVAILABLE....

62011 WEBBING NMX/HOOK HAQ-12-1-100 GID: BMBVXX

SPEC: MIL-F-21840T2C2 MIL-W-38283T4

MANF: AQM
VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	143.1	0.015		00.04	12.00	T NONE

FSC

No test data

OXYGEN COMP

No test data

06232 WEBBING NOMEX GID: BMBVXX

SPEC: MIL-W-38283T1 MIL-W-38283T2

MANF: BALLY RIBBON MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	023.8	014.5	0.020			00.10	NONE
B	1	023.8	014.5	0.020			07.50	NONE
A	1	023.8	014.5	0.055			01.50	NONE
C	1	023.8	014.5	0.019		00.31	08.00	T NONE
A	1	025.9	014.3	0.073			02.00	NONE
I	1	033.0	014.3	0.080		00.07	12.00	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	5.41	.88	2.56	

FSC

RT	FLUID NAME
A	AMMONIA

OXYGEN COMP

No test data

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	A 00022.39	

61822 WEBBING NOMEX 14.4OZ GID: BMBVXX

SPEC: MIL-W-38283T2

MANF: QSL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	023.8	014.5	0.019			00.10	NONE
C	1	023.8	014.5	0.019		00.37	12.00	T NONE

FSC

No test data

OXYGEN COMP

No test data

61823 WEBBING NOMEX 22.4OZ GID: BMBVXX

SPEC: MIL-W-38283T15

MANF: QSL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.062		00.07	12.00	T NONE

FSC

No test data

OXYGEN COMP

No test data

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006629 T

06569 WEBBING NOMEX 9476 FIREPROOFED GID: BMBVXX

MANF: BALLY RIBBON MILLS — SPEC: MIL-T-5038 MOD

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	2	025.9	014.3	0.016			00.20	NONE
B	1	025.9	014.3	0.016			11.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00020.38	

65043 WEBBING NOMEX 9960 FR GID: BMBVXX

MANF: BALLY RIBBON MILLS — SPEC: MA0105-330 — MIL-T-5608T4

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	010.0	0.004			01.40	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00022.71	

06568 WEBBING NOMEX 9981 FIREPROOFED GID: BMBVXX

MANF: BALLY RIBBON MILLS — SPEC: MIL-W-4088T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.026		00.23	12.00 T	NONE
X	2	025.9	014.3	0.042			00.30	MOD
X	1	025.9	014.3	0.042		00.20	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.2E-6	2.95	.07	2.10	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.76	

62126 WEBBING NOMEX TAPE GID: BMBVXX

MANF: BALLY RIBBON MILLS — SPEC: MIL-T-5038 ST13N868-01 — MIL-T-5038T3 ST13N868-02

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.100			01.00	NONE
A	1	025.9	014.3	0.018			03.30	NONE
A	1	025.9	014.3	0.013			00.20	NONE
I	1	025.9	014.3	0.100		00.10	10.80	NONE
A	1	033.3	014.3	0.020		00.59	12.00 T	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	2.1E-6	3.95	.06		24H-70F-

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
V	00002.36	

06642 WEBBING NOMEX/COATING FC4101-C-16 GID: BMBVXX

MANF: BALLY RIBBON MILLS — SPEC: MB0105-330 — MIL-W-4088T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.030			01.80	NONE
A	1	025.9	014.3	0.034		00.29	00.50	NONE
A	1	030.0	010.0	0.034		00.17	01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00021.90	

05286 WEBBING NYLON GID: BMBVXX

MANF: AQM — SPEC: MIL-T-8363 — MIL-W-38283T2

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006630 6

05286 WEBBING NYLON (cont)
MANF: BALLY RIBBON MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.080			01.00	NONE
X	2	025.9	014.3	0.025		00.08	12.00	T NONE
X	1	025.9	014.3	0.025		00.33	12.00	T MOD
I	1	030.0	009.0	0.020		00.22	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.2E-6	3.55	.08	2.27	

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.45	

TOXICITY

64915 WEBBING NYLON 1000 LB GID: BMBSXX
MANF: BALLY RIBBON MILLS
SPEC: MIL-T-5038

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	9.0E-7	.83	.03		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

64913 WEBBING NYLON 2300 LB GID: BMBSXX
MANF: BALLY RIBBON MILLS
SPEC: MIL-W-5625

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	9.0E-7	1.82	.10		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

64912 WEBBING NYLON 2500 LB GID: BMBSXX
MANF:
SPEC: MIL-W-4088T6

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.044		00.21	01.20	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62488 WEBBING NYLON 300 LB GID: BMBSXX
MANF: BALLY RIBBON MILLS
SPEC: MIL-T-5608TSCLC

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.58	.24		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60669 WEBBING NYLON 400 LB GID: BMBVXX
MANF: BALLY RIBBON MILLS
SPEC: MIL-C-7515T1

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.27	.10		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

64910 WEBBING NYLON 5000 LB GID: BMBSXX
MANF:
SPEC: MIL-W-4088T24

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.065		00.10	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60670 WEBBING NYLON 750 LB GID: BFCBXX
MANF: BALLY RIBBON MILLS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.12	.08		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

20347 WEBBING NYLON 7774 GID: BMBVXX
MANF: BALLY RIBBON MILLS
SPEC: ST13N070-01 ST13W619-01

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006631 8

20347 WEBBING NYLON 7774 (cont)

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.028		00.26	12.00	T MOD
X	2	025.9	014.3	0.029			02.80	MOD
X	1	025.9	014.3	0.029		00.25	12.00	T MOD

FSC

RT	FLUID NAME

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.1E-7	1.57	.06		

ODOR

RT	RT	WEIGHT	CURE
A	A	00020.41	

TOXICITY

64914 WEBBING NYLON 9000 LB GID: BMBSXX

MANF: BALLY RIBBON MILLS SPEC: MIL-W-27657T5

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.09	.26		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

02979 WEBBING NYLON FIRE/WATER PROOF GID: BMBSBS

MANF: AQM SPEC: MA0105-330 MIL-W-4088T1A

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.061			06.50	MOD
X	1	025.9	014.3	0.061		00.18	11.90	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.87	

TOXICITY

80082 WEBBING NYLON NET AAES-236/BG 168

MANF: ALL AMERICAN ENGINEERING CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	020.9	014.7	0.095		00.10	12.00	T LARGE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	600	72	540	0.060	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	2.82	.03	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

60619 WEBBING NYLON P8229 GID: BMBVXX

MANF: BALLY RIBBON MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.014			04.60	SMALL
A	1	025.9	014.3	0.014			04.80	SMALL
X	1	030.0	010.4	0.014			04.60	MOD
X	2	100.0	020.2	0.014		01.00	12.00	T MOD
X	1	100.0	020.2	0.014		03.00	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.33	

TOXICITY

02958 WEBBING NYLON TAPE

MANF: SPEC: MIL-T-5038

....NO TEST DATA AVAILABLE....

60167 WEBBING NYLON WOVEN GID: BMBSXX

MANF: SPEC: MIL-W-27265 MIL-W-27657

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006632 T

60468 WEBBING NYLON/NEOPRENE 3090 GID: BMBSHD

MANF: RESEARCH PRODUCTS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.074			00.10	NONE
X	1	025.9	014.3	0.074		00.71	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.57	.22		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.31	

61660 WEBBING NYLON/VELCRO/NOMEX/METALIZED UTILITY STRAP GID: BMBVXX

SPEC: MIL-F-21840 MIL-T-43636T12E
MIL-W-38283T2 MS27980

MANF: AQM
DUPONT
VELCRO CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.290		00.05	12.00	MOD
X	1	025.9	014.3	0.290		00.15	12.80 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06384 WEBBING PBI FRL-S169 FX GID: BMHEXX

MANF: FABRIC RESEARCH LAB

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.070		00.00	00.00	NONE
A	1	030.0	009.0	0.070		00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.2E-6	8.12	.00	7.04	24H-110F-

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	A 00017.89	

20332 WEBBING POLYESTER 1749 GID: BMCBXX

SPEC: ST11D128-01

MANF: BALLY RIBBON MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.023		00.12	12.00 T	NONE
X	1	025.9	014.3	0.023		00.41	12.00 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.1E-7	.75	.12		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
	V 00019.78	

61131 WEBBING POLYESTER 1754 GID: BMCBXX

SPEC: ST13W128-05

MANF: BALLY RIBBON MILLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	023.8	014.5	0.027			01.70	MOD
X	1	023.8	014.5	0.027			04.00	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.0E-6	.40	.15		

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
	K 00028.65	

20730 WEBBING POLYESTER 2276 ELASTIC GID: BHXXXX

MANF: PENTAPCO INC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.033		00.11	11.80 T	MOD
X	1	025.9	014.3	0.033		01.02	11.80 T	MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	4.6E-6	1.45	.34	.13	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
	A 00009.01	

06592 WEBBING POLYESTER 562 PLASTIC GID: BMCBXX

MANF: GEORGE C MOORE CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.043		00.14	12.00	T MOD
X	1	025.9	014.3	0.043		00.41	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.10	

TOXICITY

20491 WEBBING POLYESTER ELASTIC GID: BHCBXX

MANF: UNITED WEB

SPEC: ST13N613/ILC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.059			11.40	MOD
X	1	025.9	014.3	0.059		00.56	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.4E-7	1.48	.10		

ODOR

RT	RT	WEIGHT	CURE
A	V	00020.03	

TOXICITY

05434 WEBBING PRORYLENE GID: BMXXXX

....NO TEST DATA AVAILABLE....

06529 WEBBING STRAP NYLON FIRE/WATERPROOF

MANF: AQM

SPEC: MA0105-330

MIL-W-38283T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3	0.025			00.90	NONE
A	1	030.0	009.0	0.025			01.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00019.92	

TOXICITY

06415 WEBBING STRAP NYLON/FC4101 GID: BMBSGR

MANF: 3M CO

SPEC: MIL-W-38283T2

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.027		00.35	08.40	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60147 WEBBING TEXTILE ELASTIC COTTON

MANF:

SPEC: MIL-W-5664

....NO TEST DATA AVAILABLE....

60160 WEBBING TEXTILE/NYLON/TUBULAR GID: BMBSXX

MANF:

SPEC: MIL-W-5625

....NO TEST DATA AVAILABLE....

60787 WEBBING TY WD901 GID: BMCBXX

MANF: PHOENIX TRIMMING

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	4.4E-6	1.33	.77		

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

20601 WET WIPES

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006634 3

69965 WIRE CABLE SHIELDED GID: ENXXXX
MANF: ROTRONIC INSTRUMENT CORP
SPEC: MIL-W-16878/4 T S.W.

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	20.463	

62884 WIRE ELEC GID: ELXXXX
MANF: TENSOLITE
SPEC: MMS-E-737

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.050	0	20

61225 WIRE ELEC 16 AWG CABLE GID: EMXXXX
MANF: ST5M1298-16R2U0
SPEC: ST5M1298-16R2U0

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	025.9	014.3	0.012		08.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00027.90	

69928 WIRE ELEC 1871-2-169 PTFE KAPTON
MANF: FILISTER

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
C	020.9	014.7	0.137	00.00	04.50

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.0E-6	.91	.03	.80	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

62528 WIRE ELEC 2-WIRE CABLE GID: EXXXXX
MANF: BELDEN
MILIBRIDE DIV
SPEC: MIL-W-27500-24

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	025.9	014.3	0.200	00.80	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.6E-6	.02	.01	.01	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00020.33	

63382 WIRE ELEC BMS 13-46 26 AWG GID: EPXXXX

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
C	025.9	014.3	0.029	00.00	03.50

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

69933 WIRE ELEC BTV 2-26-BF-9 PTFE KAPTON
MANF: FILISTER

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	020.9	014.7	0.011	01.10	00.70

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	3.0E-6	.24	.02	.19	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

62513 WIRE ELEC CU/MYLAR/MYLARWRAP GID: EXXXXX
MANF:
SPEC: M1516F-MF2-5

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	020.9	014.70	0.010	00.90	12.30

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006635 5

64184 WIRE ELEC CU/VARGLAS/TFE GID: EPXXXX

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	100.0	044.0			05.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62880 WIRE ELEC E7371001 GID: EMXXXX

MANF: CARLISLE CORP

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.017	0	20

62525 WIRE ELEC E050A040 GID: EXXXXX

MANF: W L GORE

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	025.9	014.3		00.00	12.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00009.55	

TOXICITY

60650 WIRE ELEC ESTANE 58300 GID: EPXXXX

MANF: B F GOODRICH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	K	00020.48	

TOXICITY

60921 WIRE ELEC ESTANE 58866 INSUL GID: EPXXXX

MANF: B F GOODRICH

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
	A	00020.01	

TOXICITY

62517 WIRE ELEC ETFE TEFZEL GID: EPXXXX

MANF: CHAMPLAIN CABLE CORP
DORNIER
PRESTOLITE
RAYCHEM CORP
SINGER KEARFOTT
TELEDYNE THERMATICS

SPEC: MIL-W-22759, MIL-W-22759/18, MIL-W-81822/13, MIL-W-22759/17, MIL-W-22759/35

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	020.9	014.7	0.033	03.60	00.00
X	025.9	014.3	0.030	05.00	12.00
X	030.0	010.0	0.004	12.00	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.68	.01	.00	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

62518 WIRE ELEC ETFE WHT 20 AWG GID: EMCNXX

MANF: THERMAX WIRE CORP

SPEC: MIL-W-22759

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	020.9	014.7	0.061	01.70	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.09	.00	.06	

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006636 7

05451 WIRE ELEC FEP GID: EPBOXX

MANF: HAVEG
HY-CAL
RANGER WIRE & CABLE

SPEC: 40M39513
MIL-W-16878/13
STM-E-658
MIL-W-16878/11
MMS-E-6581010

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	020.9	014.7		00.00	00.00
I	100.0	014.5	0.056		04.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.056	0	20
B	MECH	14.7	72	-297	0.135	0	20

05236 WIRE ELEC FEP WITH POLYIMIDE TAPE GID: EPCNCD

MANF: AQM
FLUOROCARBON CORP
HUGHES AIRCRAFT
RAYCHEM CORP
TIMES FIBER

SPEC: HMS 2-2103TU
MIL-C-27500/22
MIL-W-81381/11
MB0150-051
MIL-W-81381

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
C	020.9	014.7	0.007	01.50	04.20
C	025.9	014.3	0.007	02.40	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00074.37	

05179 WIRE ELEC FEP/POLYIMIDE TAPE GID: EPCDBO

MANF: HAVEG

SPEC: MB0150-048
MIL-W-81381
MP571-0077-0003
MP571-0077-0006
MP571-0077-0010
MB0150-061
MP571-0077-0001
MP571-0077-0004
MP571-0077-0009
MP571-0084-0014

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	023.8	014.5	0.122	00.70	00.00
B	023.8	014.5	0.568	00.00	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.25	.01	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.21	

05235 WIRE ELEC FEP/POLYIMIDE TAPE GID: EPCDBO

MANF: BARCEL WIRE AND CABLE
TELEDYNE THERMATICS

SPEC: MB0150-048
MP571-0077-0001
MP571-0077-0004
MIL-W-81381/17
MP571-0077-0003
MP571-0077-0006

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	023.8	014.5	0.104	00.80	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.14	.01	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.04	

05332 WIRE ELEC FEP/POLYIMIDE TAPE GID: EPCDBO

MANF: BARCEL WIRE AND CABLE
LABARGE

SPEC: MB0150-048
MIL-W-81381
MMS-E-741
MP571-0077-0003
MP571-0077-0006
MP571-0077-0010
MP571-0086-0003
STM-E-741
MB0150-061
MMS-E-659
MP571-0077-0001
MP571-0077-0004
MP571-0077-0009
MP571-0084-0014
STM-E-659

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006637.9

05332 WIRE ELEC FEP/POLYIMIDE TAPE (cont)

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
C	020.9	014.7	0.042	00.00	06.00
B	023.8	014.5	0.097	00.80	00.00
I	030.0	010.0		01.60	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data					

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	2.4E-6	.17	.01	.13	

ODOR

RT	RT WEIGHT	CURE
A	V 00020.12	

TOXICITY

62522 WIRE ELEC FEP/POLYIMIDE TAPE GID: EPBOCD

MANF: CHAMPLAIN CABLE CORP

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	025.9	014.3	0.003		00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data					

62589 WIRE ELEC FEP/POLYIMIDE TAPE GID: EPBOCD

MANF: ENDEVCO

SPEC: MB0150-048 MP571-0087-0003

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	020.9	014.7	0.069		06.70

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data					

62591 WIRE ELEC FEP/POLYIMIDE TAPE GID: EPBOCD

MANF: AQM
ENDEVCO

SPEC: MB0150-048 MIL-W-81381
MP571-0086-0002 MP572-0310-0002

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	020.9	014.7	0.007		05.80
I	025.9	014.3	0.006		01.00
I	030.0	010.4	0.007		05.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data					

61541 WIRE ELEC FLEXIBLE PRINTED/KAPTON GID: EXXXXX

MANF: CONRAC
HUGHES AIRCRAFT

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	020.9	014.7	0.010	14.00	18.60
I	023.8	014.5		13.50	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data					

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.22	.01	.00	

ODOR

RT	RT WEIGHT	CURE
A	00019.83	

TOXICITY

64861 WIRE ELEC GWN 1328 AG PLATED GID: EXXXXX

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	020.9	014.7	0.230	01.00	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data					

62529 WIRE ELEC HEADSET 28 AWG GID: ENXXXX

MANF: TELECTNET

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	020.9	014.3	0.125	12.00	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
No test data					

60479 WIRE ELEC KAPTON FEP POLYIMIDE GID: EPXXXX

MANF:

SPEC: HMS 2-2103TU KTN 1064

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.53	.02	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

63960 WIRE ELEC KAPTON TAPE/GLASS TUBE GID: EXXXXX

MANF: GENERAL ELECTRIC SPEC: MIL-C 27500/16
RAYCHEM CORP

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	020.9	014.7	0.006		12.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

65124 WIRE ELEC KAPTON/FEP SEE RPT GID: EPXXXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
S		

65024 WIRE ELEC KAPTON/FEP SPECIAL GID: EPXXXX

MANF: SPEC: SL-20-16C

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
X	00027.62	

05449 WIRE ELEC KYNAR PVF GID: EPCTCJ

MANF: AQM SPEC: MIL-W-81822/3
GSA
RAYCHEM CORP

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	020.9	014.7	0.039	12.00	00.00
X	025.9	014.3	0.020	03.10	00.00
X	030.0	010.0	0.006	06.80	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	18.5	

65055 WIRE ELEC L/N 0000003740 GID: EPXXXX

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	10	-297	0.048	0	20

60435 WIRE ELEC LACKDRAHTW180HW11 GID: EPXXXX

MANF: LACROIX U KRESS

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	10.44	.24	.00	12H-185F- 12H-140F-0psiaVACUUM

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05093 WIRE ELEC MAGNET CL 220 GID: EPXXXX

MANF: SPEC: J-W-1177 MIL-W-583M
MN 1100 TY16C

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.78	.11	.00	

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

05322 WIRE ELEC MAGNET CL200 TYPE K POLYESTER GID: EPXXXX

MANF: AQM SPEC: J-W-1177/13 J-W-1177/14
MIL-W-583C

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	4.2E-6	.02	.01		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.99	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006339 2

06103 WIRE ELEC MAGNET POLYESTER-IMIDE OR POLYESTER-AMIDE-IMIDE CL 180 GID: EPCDXX

MANF: AQM SPEC: J-W-1177/12

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
B	4	025.9	014.3	0.018			00.00	NONE
B	1	025.9	014.3	0.018			04.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	025.9	014.3	0.018	04.00	00.00

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	.89	.11	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

69825 WIRE ELEC MD 913 FLUOROCARBON POLYIMIDE INSULATION

MANF: TIMES FIBER SPEC: MIL-W-27500/20

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	024.5	014.5	0.100			00.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	024.5	014.5	0.100	00.50	00.00

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.75	.05	.58	

ODOR

RT	RT WEIGHT	CURE
K	22.321	

TOXICITY

69927 WIRE ELEC MTV TYPE/PTFE KAPTON INSULATION

MANF: FILISTER

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
C	020.9	014.7		00.70	10.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.04	.00	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

80299 WIRE ELEC P/N OM365474-1 GID: ELXXXX

MANF: MOTOROLA

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	025.9	014.7	0.035	01.50	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
K	2.55	

TOXICITY

63962 WIRE ELEC PD-219-21 GID: EPCTXX

MANF: ITT CANNON SPEC: MIL-W-81044/12

....NO TEST DATA AVAILABLE....

62524 WIRE ELEC PEEK (POLYETHER-ETHERKETONE) GID: BCXXXX

MANF: COLYER

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
C	020.9	014.7	0.045	02.20	03.10
I	030.0	010.0	0.009		06.10

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.6E-6	.04	.02	.03	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006640 9

63966 WIRE ELEC POLYETHYLENE GID: EPXXXX

MANF: BELDEN

SPEC: MIL-W-16878/10

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	020.9	014.7	0.012		03.20

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	00022.06	

65549 WIRE ELEC POLYIMIDE INSULATION GID: EPXXXX

MANF: TIMES FIBER

SPEC: MD921-20
NE-1-M-12

MIL-C-27500/20

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	024.5	014.5		00.90	02.70

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	.63	.04	.49	

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
K	22.14	

63311 WIRE ELEC POLYIMIDE/KYNAR RT850

MANF: RAYCHEM CORP

SPEC: MSFC SPEC 276

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	025.9	014.3		01.50	12.00

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data						

62532 WIRE ELEC POLYURETHANE 8771 GID: EPCQXX

MANF: BELDEN

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	020.9	014.7	0.170	02.10	13.00

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data						

05991 WIRE ELEC PT COND/MGO INS/MET GID: EPXXXX

....NO TEST DATA AVAILABLE....

05732 WIRE ELEC PTFE/GLASS FEP GID: EPCNIA

MANF: A E PETSCHE CO
DORNIER

SPEC: MIL-W-22579/3
MIL-W-22759/1

MIL-W-22759 1-18-9
MIL-W-22759/4

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
C	020.9	014.7	0.050	03.20	11.40
X	030.0	010.0	0.150	12.00	

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.1E-6	.02	.01	.01	

ODOR

RT
A

TOXICITY

RT	RT WEIGHT	CURE
A	00020.06	

20756 WIRE ELEC PVC GID: EPAEXX

MANF: BELDEN
CALMONT
KALAS MFG
RAYCHEM CORP

SPEC: AB0150-023-26-1
SS-24-301

MIL-W-16878/1

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	020.9	014.7	0.037		00.00
X	025.9	014.3	0.100	12.00	12.00

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	RT WEIGHT	CURE
X	00030.77	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006641 0

63965 WIRE ELEC PVC INSULATED POLYAMIDE JACKET GID: EPXXXX

MANF: BELDEN

SPEC: MIL-W-16878/17

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	020.9	014.7	0.140		00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	21.46	7.23	.00	

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00022.05	

20908 WIRE ELEC PVC-A GID: EPAEXX

MANF: TELEDYNE THERMATICS
TIMES WIRE & CABLE

SPEC: MIL-C-17/RG-58

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	020.9	014.7	0.015	01.80	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data						

62574 WIRE ELEC PYRAD 1000 GID: EPFVXX

MANF: HAVEG

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	020.9	014.7	0.049	00.60	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.3E-6	.07	.00		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

20258 WIRE ELEC R4800/TY P222,P229 GID: FJXXXX

....NO TEST DATA AVAILABLE....

20877 WIRE ELEC RAYCHEM 44 ALL GAGES

MANF: ITT CANNON
RAYCHEM CORP
SEE TEST REPORT

SPEC: MB0150-066
MIL-W-81044
PD-219-21

MB0150-066/12
MIL-W-81044/12

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
C	020.9	014.7	0.087	12.00	13.00
C	023.8	014.5		01.30	18.30
C	024.5	014.7	0.046	12.00	12.00
C	025.9	014.7	0.052	12.00	
C	030.0	009.0	0.054	12.00	

FSC

RT	FLUID NAME
A	HYD
A	HYZE
C	N2O4

OXYGEN COMP

RT	TEST PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data						

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.35	.07	.27	130H-203F-

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00021.71	

63306 WIRE ELEC RAYCHEM 44 BETAWRAP GID: EXXXXX

MANF: DODGE
RAYCHEM CORP

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	024.5	014.3	0.500	00.25	
X	025.9	014.3	0.010		27.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data						

63955 WIRE ELEC RAYCHEM 44 FABRIC/MESH GID: EPCBXX

MANF: RAYCHEM CORP

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	020.9	014.7	0.010		00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data						

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006642 2

60710 WIRE ELEC RAYCHEM 44 MYLAR/KAPTON GID: EPXXXX

MANF: GENERAL ELECTRIC SPEC: MIL-C-27500/16 MIL-W-22759 18-20-9
RAYCHEM CORP MIL-W-22759 32-20-9

ELECTRICAL WIRE & ACCESSORIES						FSC	OXYGEN COMP				
RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	020.9	014.7	0.010	00.00	12.00	No test data	No test data				

62598 WIRE ELEC RAYCHEM 44 SHIELD/INSULATION GID: EXXXXX

MANF: RAYCHEM CORP

FLAMMABILITY									FSC	OXYGEN COMP					
RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7				01.30	NONE	No test data	No test data				
A	1	020.9	014.7	0.058			01.30	NONE						
A	1	020.9	014.7	0.058		00.00	00.00	NONE						

ELECTRICAL WIRE & ACCESSORIES					
RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	020.9	014.7	0.039	06.20	01.30
C	024.5	014.3	0.034	12.00	00.00

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.8E-6	.11	.01	.01		No test data		

62499 WIRE ELEC RAYCHEM 44 WITH ATLAS TUBE GID: EXXXXX

MANF: RAYCHEM CORP
ZIPPERTUBING

ELECTRICAL WIRE & ACCESSORIES						FSC	OXYGEN COMP				
RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
I	025.9	014.3	0.008		00.00	No test data	No test data				

62498 WIRE ELEC RAYCHEM 44 WITH FEP TUBING GID: EXXXXX

MANF: RAYCHEM CORP
ZIPPERTUBING

ELECTRICAL WIRE & ACCESSORIES						FSC	OXYGEN COMP				
RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
X	025.9	014.3	0.009		13.00	No test data	No test data				

62510 WIRE ELEC RAYCHEM 44/KAPTON GID: EXXXXX

MANF: GENERAL ELECTRIC SPEC: MIL-C-27500
RAYCHEM CORP

ELECTRICAL WIRE & ACCESSORIES						FSC	OXYGEN COMP				
RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
C	020.9	014.7	0.150	01.10	07.30	No test data	No test data				

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	.17	.07	.00		No test data		

62495 WIRE ELEC RAYCHEM 55 ETFE GID: EPXXXX

MANF: RAYCHEM CORP

ELECTRICAL WIRE & ACCESSORIES						FSC	OXYGEN COMP				
RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4	RT FLUID NAME	RT TEST PRESS	IMPACT TEMP	THICK	#REACT	#TEST
B	020.9	014.7	0.043	02.00	09.20	No test data	No test data				
B	024.5	014.3	0.044	02.00	00.00						
B	025.9	014.3	0.037		01.50						

THERMAL VACUUM STABILITY					ODOR	TOXICITY	
RT	PRESS	TML%	VCM%	RML%	CURE	RT	RT WEIGHT	CURE
A	1.0E-6	00.03	.00	.00		A	A 00020.56	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006643 4

63958 WIRE ELEC RAYCHEM CU/MYLAR/KAPTON GID: ELCDCC

MANF: GENERAL ELECTRIC
RAYCHEM CORP

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	020.9	014.7	0.010		08.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63415 WIRE ELEC REINSHAGEN POLYIMIDE GID: EPCDXX

MANF: ESA

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	024.5	014.5		03.00	
C	025.9	014.3		02.00	04.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

69810 WIRE ELEC SAMPLES V6.N22-9

MANF: CONSOLIDATED CONTROLS

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
No test data								

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.048	00	20

62575 WIRE ELEC SILICONE RUBBER 20 AWG GID: EPDPXX

MANF: RCA

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	025.9	014.5	0.170	12.00	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	1.25	.28	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

05378 WIRE ELEC TEFLON PFA GID: EPCNXX

SPEC: MB0150-062

MANF: COLYER
TELEDYNE THERMATICS

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	023.8	014.5	0.200		00:00
I	030.0	010.0	0.007	02.20	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
A	A 00020.17	

TOXICITY

05275 WIRE ELEC TEFLON TFE GID: EPCNXX

MANF: AMETEK
AQM
BELDEN
CARLISLE CORP
CERRO WIRE & CABLE
DORNIER
HAVEG
HAVEY INSULATION
HUGHES AIRCRAFT
HY-CAL
IMPERIAL WIRE & CABLE
RAYCHEM CORP
REYNOLDS
ROCKWELL
SHELDAHL
TELEDYNE BROWN ENG

SPEC: 40M39513
55A6005
HMS 2-2103TSJ
MIL-C-572
MIL-W-16878/25
MIL-W-22759
MIL-W-25038
MMS-E-300
MMS-E-300-2003
MMS-E-3002202
MMS-E-658 1002
MMS-E-6581002
MP572-0279-002
STM-E-2202B
STM-E-300-1
STME 643
55A0811-22
AB0150-006
MIL-C-27500
MIL-W-16878-E
MIL-W-16878/25BFE9
MIL-W-22759/4
MIL-W-81381
MMS-E-300-2002
MMS-E-300-2202
MMS-E-654 1010
MMS-E-658 1009
MMSE 8432129
STM 6372439
STM-E-300
STM-E-658
STME 7192009

MSFC-HDBK-527 REV F 9999942 0006644 6

Information Handling Services, 2000

05275 WIRE ELEC TEFLON TFE (cont)

MANF: TENSOLITE

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	020.9	014.7	0.074	01.40	01.00
I	023.8	014.1	0.330	00.00	
B	025.9	014.3	0.076	01.20	03.00
B	030.0	010.4	0.074	01.20	01.00
I	033.0	014.3	0.053	12.00	
X	100.0	042.0		12.00	12.00

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
B	MECH	14.7	72	-297	0.048	0	20
B	MECH	14.7	72	-297	0.050	0	60
B	MECH	14.7	72	-297	0.130	0	20
B	MECH	14.7	72	-297	0.145	0	20

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	7.9E-7	1.24	.20		

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00041.67	

06547 WIRE ELEC TFE MINERAL FILLED GID: EPCNFW

MANF: A E PETSCHE CO

SPEC: MIL-W-22759/5 MIL-W-22759/6 MIL-W-22759/7 MIL-W-22759/8

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.1E-6	.03	.03	.01	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00020.02	

63421 WIRE ELEC TFE/GLASS WARP GID: EPCNFV

MANF: IMPERIAL WIRE & CABLE

SPEC: MMS-E-646 STM-E-646 MMSE6462202

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	100.0	042.0	0.200	09.50	10.00

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

02816 WIRE ELEC TFE/ML ENAMEL GID: EPCNXX

MANF: QSL

SPEC: MB0150-035 STM-E-921

....NO TEST DATA AVAILABLE....

05212 WIRE ELEC TFE/ML ENAMEL GID: EPCNXX

MANF: HAVEG

SPEC: MB0150-061

....NO TEST DATA AVAILABLE....

05318 WIRE ELEC TFE/ML ENAMEL GID: EPCNXX

....NO TEST DATA AVAILABLE....

64822 WIRE ELEC TFE/SARAN WRAPPED GID: DUXXXX

MANF: DOW CHEMICAL

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	020.9	014.7		02.60	

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63310 WIRE ELEC THERMOCOUPLE FIBERGLASS GID: EPFVXX

MANF: AQM
GORDON SERV-RITE
IMPERIAL WIRE & CABLE

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
C	100.0	042.0	0.042	03.00	12.00

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60651 WIRE ELEC TRIAXIAL GID: EPXXXX

MANF: RAYCHEM CORP

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	020.9	014.7	0.132	01.40	00.00

FSC

RT	FLUID NAME
	No test data

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

MSFC-HDBK-527 REV F 9999942 0006645 8

60651 WIRE ELEC TRIAXIAL (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.2E-6	.16	.02	.04	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

62599 WIRE ELEC URETHANE 29 AWG GID: EMXXXX

MANF: CALMONT

SPEC: SEC329U-BWU

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	030.0	010.0	0.100	12.00	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
A	A	00021.39	

62527 WIRE ELEC VARGLAS SLEEVE GID: BCXXXX

MANF: NIKON
VARFLEX CORP

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
C	025.9	014.3	0.185	07.30	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62582 WIRE ELEC VARGLASS SLEEVE 20AWG GID: EPCNIA

MANF: MARTIN MARIETTA

SPEC: STM-F-203

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	100.0	044.0	0.180		00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	MECH	14.7	72	-297		0	20
I	MECH	44	72	70		0	20

62514 WIRE ELEC WITH FIBERGLASS SLEEVE GID: EMFWXX

MANF: GENERAL ELECTRIC
RAYCHEM CORP

SPEC: MIL-C-27500

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	020.9	014.7	0.013		11.30

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

62512 WIRE ELEC WITH METAL BRAID SHIELD GID: EPXXXX

MANF: GENERAL ELECTRIC
RAYCHEM CORP
TELEDYNE THERMATICS

SPEC: MIL-W-22759 18-20-9

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	020.9	014.7	0.008	00.00	01.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	A	16.0	

65503 WIRE ELEC WITH POLYIMIDE INSULATION GID: EPXXXX

MANF: LOCKHEED

SPEC: EH32 (86-285)
EH32 (86-288)
MD920-20-6
MD920-8
MIL-W-81381/17-20-X
EH32 (86-286)
MD920-12-4
MD920-22-1
MIL-W-81381/11-8
MIL-W-81381/17-22-X

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
B	024.5	014.5		00.00	00.00
B	024.9	014.5	0.093	00.00	00.00

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	6.0E-6	1.20	.05	.67	

ODOR / TOXICITY

RT	RT	WEIGHT	CURE
	K	21.97	

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006646 T ■

85477 WIRE ELEC WRAPPED IN P2650 SILICONE TAPE

MANF: AQM
PERMACEL

SPEC: MMS-E-741 STM-E-741

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7				00.13	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
I	020.9	014.7		00.13	

06225 WIRE ELECTRIC FIBERGLASS GID: FJFVXX

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
A	1.0E-6	.55	.10	.00	

ODOR

RT	RT WEIGHT	CURE
No test data		

TOXICITY

63776 WIRE GSC 1620 GID: ELXXXX

MANF: W L GORE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT WEIGHT	CURE
X	02271.50	

TOXICITY

64813 WIRE HEATER MC363-0031 0038 GID: EPXXXX

MANF: COX & CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	025.9	014.3				00.30	SMALL
A	1	033.0	014.3				01.40	SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63246 WIRE JUMPER NYLESE/PC18M COATED

MANF:

SPEC: J-W-1177/9

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	030.0	009.0	0.020			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

63145 WIRE MAGNET NYLON/POLYURETHANE GID: EPBSC

MANF:

SPEC: J-W-1177/9

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.022			07.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

20651 WIRE MAGNET P/N 1600E-056B-013

MANF: MAGNET TECHNOLOGY

....NO TEST DATA AVAILABLE....

85401 WIRE MAGNET RECTANGULAR POLYVINYL FORMAL COATED CLASS 105 TYPE 2 AND 4

MANF: AQM

SPEC: J-W-1177A MIL-W-583

....NO TEST DATA AVAILABLE....

80054 WIRE P1W C-7 POLYIMIDE GID: EPCDXX

MANF: SHOWA ELECTRIC WIRE & COMPANY

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	4	024.5	014.5				05.80	NONE
A	1	024.5	014.5				01.10	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ELECTRICAL WIRE & ACCESSORIES

RT	%OXY	PRESS	THICK	BURNLGTH1	BURNLGTH4
X	024.5	014.5		01.10	05.80

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006647 1

80054 WIRE P1W C-7 POLYIMIDE (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	22.058	

64874 WIRE STYLE 2850/SCOTCH 280 GID: EXXXXX

....NO TEST DATA AVAILABLE....

69949 WIRE ZINC METALLIZING SPEC: MIL-W-6712C

MANF:

....NO TEST DATA AVAILABLE....

06552 WOOD SOFT COMMERCIAL

MANF: AQM

....NO TEST DATA AVAILABLE....

20676 WRISTLETS P/N A7L-101121-01 GID: DDXXXX

MANF: GSA

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
A	00029.50	

05909 XIRCONIA ZRO2 (INORG)

....NO TEST DATA AVAILABLE....

60412 XR-5236

....NO TEST DATA AVAILABLE....

60868 YARN 200-100-R79-430 NOMEX GID: EDBVXX

MANF: DUPONT

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.7E-6	3.56	.11		

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

06168 YARN GLASS/TFE SF-542 GID: EUGDCN

MANF: SANTA FE TEXTILES

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.120			02.30	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.2E-6	.26	.11		

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
A	00019.98	

05867 YARN KELVAR 29 TYPE 964 GID: EDJHXX

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	030.0	010.0	0.025		0.2	10.80	SMALL
X	1	030.0	010.0	0.025		1.2	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	1.0E-6	3.25	.17	.00	

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	20.621	

61408 YARN NOMEX R79-430 GID: BFBVXX

SPEC: MIL-T-43636/1E

MANF: DUPONT

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	010.0	0.003		03.50	12.00	T SMALL

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006648 3

61408 YARN NOMEX R79-430 (cont)

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.0E-7	2.93	.08		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.75	

63247 YARN POLYESTER 1100 DENIER GID: EUCBXX

MANF: TELEDYNE BROWN ENG SPEC: MIL-C-572

FLAMMABILITY / FSC / OXYGEN COMP

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
I	2	020.9	014.7	0.005			01.50	NONE	No test data		No test data							
I	2	024.5	014.5	0.005			03.00	NONE										
A	2	030.0	010.0	0.005			06.50	NONE										
A	1	030.0	010.0	0.005		00.44	04.70	NONE										

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.4E-6	2.13	.00	.10	

ODOR / TOXICITY

RT	RT WEIGHT	CURE
No test data		

20328 YARN STYLE 7511 GID: BFXXXX

MANF: FWF IND INC SPEC: ST14N099-01

FLAMMABILITY / FSC / OXYGEN COMP

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
X	2	025.9	014.3	0.151		00.09	12.00	T MOD	No test data		No test data							
X	1	025.9	014.3	0.151		00.27	12.00	T MOD										

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	8.2E-7	1.66	.22		

ODOR / TOXICITY

RT	RT WEIGHT	CURE
A	A 00020.08	

02112 YARN TFE TYPE 302 GID: EDCNXX

MANF: DUPONT SPEC: MIL-I-45208A

FLAMMABILITY / FSC / OXYGEN COMP

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	023.8	014.5	0.015			04.90	NONE	No test data		No test data							

20900 Z 40MXXXX CONNECTOR

....NO TEST DATA AVAILABLE....

80004 Z CONFIG ACCEPTION

MANF: ROCKWELL SPEC: MA0605-303

FLAMMABILITY / FSC / OXYGEN COMP

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN	RT	FLUID NAME	RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
A	1	020.9	014.7				02.00	SMALL	No test data		No test data							

20901 Z EEE NO OPERATIONAL PART

....NO TEST DATA AVAILABLE....

20902 Z EEE OPERATIONAL PART

....NO TEST DATA AVAILABLE....

80005 Z GFE

....NO TEST DATA AVAILABLE....

00000 Z MATERIALS SHOWN ON LOWER ASY

....NO TEST DATA AVAILABLE....

50075 Z MATL AGED OR HEAT TREATED

....NO TEST DATA AVAILABLE....

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006649 5

80008 Z MATL ID ON PROD PART
....NO TEST DATA AVAILABLE....

80001 Z MATL ID ON SUBCONTRACTR WKSH
....NO TEST DATA AVAILABLE....

30888 Z MATL/PART TO BE CHGD-METAL
....NO TEST DATA AVAILABLE....

20888 Z MATL/PART TO BE CHGD-NONMETL
....NO TEST DATA AVAILABLE....

30999 Z METALLIC MATL REQ EVAL
....NO TEST DATA AVAILABLE....

80006 Z NON-HAZARDOUS FLUID
....NO TEST DATA AVAILABLE....

80009 Z NOT TO BE USED ON SHUTTLE
....NO TEST DATA AVAILABLE....

40000 Z ONE TIME USE/INSUF DATA
....NO TEST DATA AVAILABLE....

80007 Z STANDARD COMM AND ME PART ID
....NO TEST DATA AVAILABLE....

80000 Z STD AND COMMERCIAL PARTS
....NO TEST DATA AVAILABLE....

80002 Z SUBSTITUTION INFO PRESENT
....NO TEST DATA AVAILABLE....

61025 ZIPPER 32" 5283-021B-4A40-0030 GID: BNBVXX SPEC: ST16N1264-10
MANF: SCOVILL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.026			09.70	NONE
C	1	025.9	014.3	0.026		00.31	12.00	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.0E-6	3.40	.35	1.98	

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
A

TOXICITY

RT	WEIGHT	CURE
K	00059.68	

61570 ZIPPER ASSEMBLY NOMEX GID: BNBVXX
MANF: SCOVILL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
C	2	025.9	014.3	0.027			00.20	NONE
C	1	025.9	014.3	0.027		00.47	12.90	T NONE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
X	6.0E-6	3.62	.13		

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

ODOR

RT
No test data

TOXICITY

RT	WEIGHT	CURE

02961 ZIPPER BRASS/COTTON GID: BNGIFS
MANF: UNITED TEXTILE

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT

TOXICITY

RT	WEIGHT	CURE
K	00071.22	

Information Handling Services, 2000

60658 ZIPPER BRASS/NYLON/MYLAR GID: FCBVXX

MANF: SCOVILL

SPEC: ST11N1264-13

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.025		00.10	16.00	T MOD
X	1	025.9	014.3	0.025		00.40	16.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	1.3E-6	3.54	.29	2.27	

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.04	

TOXICITY

63023 ZIPPER NOMEX COATED WITH RTV 6-1104 GID: AKBVXX

MANF: GOODYEAR

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	023.8	014.5	0.025		00.10	12.00	T NONE
I	1	025.9	014.5	0.025		00.15	12.00	T NONE
A	1	030.0	009.0	0.020		00.10	08.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
B	1.0E-6	.19	.01	.00	168H-70F-

ODOR

RT	RT	WEIGHT	CURE
No test data			

TOXICITY

63250 ZIPPER NOMEX VF106 GID: BNBVXX

MANF: GOODYEAR

SPEC: STD AN 229

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5	0.017			04.00	NONE
B	1	025.9	014.3	0.018			07.80	NONE
I	1	030.0	009.0	0.018		00.20	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

06250 ZIPPER NOMEX/BRASS GID: BNBVCJ

MANF: SCOVILL
TALON
TEXTRON

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	025.9	014.3	0.102		00.38	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
I	1.6E-6	5.00	.65		

ODOR

RT	RT	WEIGHT	CURE
	A	00020.38	

TOXICITY

06566 ZIPPER NOMEX/BRASS FIRE/WATER PROOF GID: BNCDXX

MANF: 3M CO
ROCKWELL
TALON

SPEC: MA0105-330

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	020.9	014.7	0.024			01.50	NONE
A	1	025.9	014.3	0.024			01.50	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00019.90	

TOXICITY

63248 ZIPPER NOMEX/COATING VITON B50 GID: BNBVXX

MANF: GOODYEAR

SPEC: V-F-106 AN 229

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
I	1	030.0	009.0	0.025		00.04	12.00	T NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

Information Handling Services, 2000

60647 ZIPPER NYLON CHAIN 10VF GID: BNBSXX
MANF: YKK ZIPPER CO
SPEC: ST16Z1838-01ILC

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	1	025.9	014.3	0.166		00.40	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

60606 ZIPPER NYLON/POLYESTER WHITE
....NO TEST DATA AVAILABLE....

62401 ZIPPER POLYESTER/DELRIN VFC 56 GID: BNCBXX
MANF: YKK ZIPPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	100.0	022.0	0.024		01.50	12.00	T MOD
X	1	100.0	022.0	0.024		02.30	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	X	00022.41	

TOXICITY

20410 ZIPPER POLYESTER/NYLON COGS GID: BNCBBS
MANF: TALON

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
No test data					

ODOR

RT	RT	WEIGHT	CURE
A	A	00016.15	

TOXICITY

03472 ZIPPER TALON 705-19 NYLON/BRASS GID: BNBSXX
MANF: TALON
SPEC: ST16F599 ST16N112-06

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.070		00.06	13.60	T NONE
X	1	025.9	014.3	0.070		00.90	13.50	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	5.0E-7	2.55	.05		

ODOR

RT	RT	WEIGHT	CURE
A	A	00019.92	

TOXICITY

61053 ZIPPER TFE/FIBERGLASS/NOMEX GID: BNCNFV
MANF: FABRIC RESEARCH LAB
SCOVILL

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
A	1	023.8	014.5			00.00	00.00	NONE

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

61049 ZIPPER YGC 459 GID: BNBSXX
MANF: YKK ZIPPER CO

FLAMMABILITY

RT	TEST	%OXY	PRESS	THICK	SUBST	COMBRT	BURNLGTH	DRPBRN
X	2	025.9	014.3	0.020			01.80	NONE
X	1	025.9	014.3	0.020		00.36	12.00	T MOD

FSC

RT	FLUID NAME
No test data	

OXYGEN COMP

RT	TEST	PRESS	IMPACT	TEMP	THICK	#REACT	#TEST
No test data							

THERMAL VACUUM STABILITY

RT	PRESS	TML%	VCM%	RML%	CURE
C	2.2E-6	.49	.15	.15	

ODOR

RT	RT	WEIGHT	CURE
A	K	00020.11	

TOXICITY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006652 5

TABLE 2B

NONMETALS BY SPECIFICATION

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
13X00526	COATING DC 92-046
13X00526 P2.0	RUBBER SILICONE DC93-076
13X00527	RUBBER SILICONE DC93-076
13X00527 P1.0	SEALANT POLYSULFIDE PR1422
13X00527 P2.0	RUBBER SILICONE DC93-076
13X00528	COATING 443-3-17 BLACK EPOXY
13X00528 1.7	COATING 443-3-1 WHITE EPOXY
13X00528 P1.6	COATING 463-6-3 GREEN EPOXY
13X00528 P3.3	PRIMER ZINC-SELE 9334 GREEN
16A10132	COATING 463-6-3 GREEN EPOXY
16A10228	COATING POLYURETHANE 710 EPOXY BLACK
16A10229	COATING POLYURETHANE 100 EPOXY WHITE
17A4629 T2	COMPOUND THERMAL CONDUCTIVE URETHANE SMRD 902
2269-01 FM5055M	LAMIN CARBON/PHENOLIC 2269-01
40M37569	ELECTRICAL CONNECTOR WITH MOLD COMPOUND RX660
40M38277	CONNECTOR ELECTRICAL
40M38277/39565	CONNECTOR 40M RECEPTACLE/PLUG
40M38277REVEO#4	CONNECTOR ELECTRICAL
40M38298	ELECTRICAL CONNECTOR WITH MOLD COMPOUND RX660
40M39513	WIRE ELEC FEP
	WIRE ELEC TEFLON TFE
40M39569	CONNECTOR ELECTRICAL
	ELECTRICAL CONNECTOR WITH FIBERITE FM4051
40M39569REVCE04	CONNECTOR 40M MODIFIED
40M39569REVCEO4	CONNECTOR ELECTRICAL
55A0811-22	WIRE ELEC TEFLON TFE
55A6005	WIRE SLEC TEFLON TFE
55L2-9	TEFLON PTFE DISCS
9M03925	TAPE SCOTCH 838 TEDLAR
9M03235-1	COATING A276 WITH PGEA/515700/910704
9M03839	FABRIC KEVLAR GAC-RF443
A22035 (BASIC)	MOOG A22035 LUBRICANT
AB0120-068CZRVC	ADHESIVE THERMAL CONDUCT SILICONE
AB0130-010 C3	ADHESIVE EPON 828/DTA EPOXY
AB0130-010-C3	ADHESIVE EA828/VERSAMID 115 EPOXY
AB0130-043	LAMIN EPOXY/GLASS EG752
AB0130-125	LAMIN EPOXY/GLASS/DC3140 COATED
AB0150-006	WIRE ELEC TEFLON TFE
AB0150-023-26-1	WIRE ELEC PVC
AB0190-004 T2	LABEL IDENTIFICATION MYLAR ADHESIVE 850 CLEAR
	LABEL IDENTIFICATION MYLAR ADHESIVE 850/ RED
	LABEL IDENTIFICATION MYLAR ADHESIVE 850/ SILVER
	LABEL IDENTIFICATION MYLAR ADHESIVE 853/ CLEAR
AH058626	ADHESIVE DC281 SILICONE WITH CATALYST
AH058905	ADHESIVE DC281 SILICONE WITH CATALYST
AMI-B3-A	CIRCUIT BREAKER HEINEMAN
AMS 2481	COATING PHOSPHATE (INORGANIC)
AMS 2515	COATING 851-225 BLK/850-201

SPECIFICATION	DESIGNATION
AMS 3195	RUBBER COHRLASTIC 10480 SILICONE
	RUBBER COHRLASTIC R10470 SILICONE
	RUBBER SILICONE 200A
	RUBBER SILICONE RTV 560
	RUBBER SILICONE RTV 560 COMPOS
	RUBBER SILICONE WITH WIRE MESH
	SPONGE RUBBER SILICONE
	TUBING FERREX 01-0504 SILICONE
AMS 3196	RUBBER COHRLASTIC R10470 SILICONE
	SPONGE RUBBER SILICONE
AMS 3198	SPONGE RUBBER NEOPRENE OPEN CELL 2-S-198
AMS 3208	RUBBER NEOPRENE
AMS 3209	CLAMP MS21919 WDG NEOPRENE
	RUBBER NEOPRENE C147-70
	RUBBER NEOPRENE C557-70
AMS 3215	RUBBER NITRILE
AMS 3238	RUBBER BUTYL
	RUBBER BUTYL B318-70
AMS 3239	RUBBER BUTYL
AMS 3241	RUBBER NEOPRENE R/C1960
AMS 3285	FELT WOOL
AMS 3301	RUBBER SILICONE HARDNESS SHORE "A" 35-45
	RUBBER SILICONE HARDNESS SHORE "A" 55-65
	RUBBER SILICONE HT 2-80 SHOCK ISOLATOR
	RUBBER SILICONE PRE100-40R
	RUBBER SILICONE S469-40
	RUBBER SILICONE S571
	RUBBER SILICONE TH1241
AMS 3302	GASKET SILICONE/AL RFI 04-0102
	RUBBER SILICONE SONFARREL 1151
	RUBBER SILICONE TH1242/TH1165
	SEALANT SILICONE/DACRON HAVEG F717/720
AMS 3302D	RUBBER SILICONE HARDNESS SHORE "A" 45-55
AMS 3303	RUBBER SILICONE EXTREME LOW TEMPERATURE
	LOW TEMPERATURE HARDNESS SHORE "A" 65-75
	RUBBER SILICONE HARDNESS SHORE "A" 55-65
	RUBBER SILICONE TH1243/TH1166
AMS 3304	RUBBER COHRLASTIC 700 SILICONE
	RUBBER SILICONE 89780
	RUBBER SILICONE HARDNESS SHORE "A" 65-75
	RUBBER SILICONE O-RINGS
	RUBBER SILICONE S604-70
AMS 3315	FABRIC GLASS/SILICONE
	FABRIC SILICONE/GLASS 3010
AMS 3315C	FABRIC SILICONE/GLASS 3016
AMS 3320	FABRIC GLASS/SILICONE
	FABRIC SILICONE 1 GLASS
AMS 3325	RUBBER SILICONE O-RINGS
AMS 3326	RUBBER FLUOROSILICONE L449-65
AMS 3327	RUBBER SILICONE NE6071/6071
	SPONGE RUBBER SILICONE
AMS 3332	RUBBER SILICONE 15130
AMS 3335	RUBBER SILICONE RTV 651
AMS 3337	RUBBER SILICONE HARDNESS SHORE "A" 55-65
	RUBBER SILICONE S383-70

MSFC-HDBK-527 REV F 9999942 0006654 9

Information Handling Services, 2000

NON-METALS DESIGNATIONS BY SPECIFICATION

SPECIFICATION	DESIGNATION
AMS 3345	FABRIC GLASS/SILICONE
	RUBBER SILICONE 1000PSI HARDNESS 45 - 55
AMS 3348	RUBBER SILICONE 30 SHORE
AMS 3377	RUBBER SILICONE NE6071/6071
AMS 3587	TUBING INSULTITE VFP876 HST BLACK
AMS 360	KEL-F CTFE UNPLASTICIZED
AMS 3612	FILM MYLAR TYPE A
AMS 3632	TUBING INSULTITE KYNAR HST CLEAR NOC
	TUBING KYNAR RT850 HST
AMS 3636-37	TUBING FP301 INSULTITE HST
AMS 3638	TUBING FP301 TYPE 2 POLYOLEFIN HS
AMS 3645	KEL-F CTFE UNPLASTICIZED
AMS 3646	KEL-F 6061-T6 10% GLASS
	KEL-F 81
AMS 3647	FILM TEFLON FEP T160
AMS 3649	FILM ACLAR 33F CTFE
	KEL-F CTFE UNPLASTICIZED
AMS 3650	KEL-F 81
	KEL-F CTFE UNPLASTICIZED
AMS 3650A	KEL-F 81
	KEL-F 81 EXPANDED/BLUE BEADING
	KEL-F 81 PV 506 GASKET
AMS 3651	TEFLON TFE VIRGIN
	TEFLON TFE/15% GRAPHITE
AMS 3651C	TEFLON TFE VIRGIN
AMS 3654	KEL-F CTFE UNPLASTICIZED
	TUBING TEFLON TFE HST
AMS 3689	ADHESIVE FILM FM40
AMS 3839	TEFLON ASBESTOS IMPREGNATED
AMS 3902	FABRIC KEVLAR 49
AMS 5525	PLATING GOLD ON A-286
AMS 7270	RUBBER NITRILE FUEL RESISTANT
AMS 7271	RUBBER NITRILE N506-65
AMS 7273	RUBBER FLUOROSILICONE
AMS 7276	RUBBER FLUOREL FC2174
	RUBBER VITON FLUID RESISTANT
	RUBBER VITON V779-75
AMS 7280	RUBBER FLUOREL FC2174
AND 63503	VESPEL SP21
AND 64927	VESPEL SP21
AP2712	RUBBER BUTYL
AS180-008	RUBBER VITON FLUID RESISTANT
AS180-010	RUBBER VITON FLUID RESISTANT
AS180-012	RUBBER VITON FLUID RESISTANT
AS180-014	RUBBER VITON FLUID RESISTANT
AS180-017	RUBBER VITON FLUID RESISTANT
AS180-018	RUBBER VITON FLUID RESISTANT
AS180-022	RUBBER VITON FLUID RESISTANT
	RUBBER VITON O-RING
AS180-116	RUBBER VITON FLUID RESISTANT
AS180-222	RUBBER VITON FLUID RESISTANT
AS180-228	RUBBER VITON FLUID RESISTANT
AS180-230	RUBBER VITON FLUID RESISTANT
ASTM 2AA508A13	BLADDER BUTYL RUBBER
ASTM D-2000	RUBBER SILICONE GR 2

SPECIFICATION	DESIGNATION
ASTM D1056-68	SPONGE RUBBER NEOPRENE
ASTM D1457	HOSE NYLON/TEFLON R531-4
ASTM D1457 T3	LINER HOSE AE 116-8/AE 121-4
	LINER HOSE AE 246-10/667-16
ASTM D1755	PLASTIC POLYVINYL CHLORIDE (PVC)
ASTM D2000	RUBBER NEOPRENE
	RUBBER SILICONE E6132
ASTM D2000BA715	RUBBER EPR 3177
ASTM D2000BC415	RUBBER CHLOROPRENE CPD 2408A
ASTM E 595-77	MOLD COMPOUND E-21718/X49560
ASTM E595-77	FABRIC NYLON URETHANE COATED
AT8598	CLIPS CORD B2
B-13,C12,F19	RUBBER EPR 3177
B13C12F19	RUBBER EPR 3177
B20808	LEAK DETECTOR SHERLOCK 5 SEC
BMO135-048 T3	FILM G145100 .5 MIL KAPTON .9 OZ PER SQUARE YARD NOMEX SCRIM
BMS-161-756	COMPOSITE REINFORCEMENT
BMS10-21C TY1	COATING CONDUCTIVE 463-6-14
BURNDY ML120T-6	COATING ACRYLIC PC20/20M
C-85052	CLAMP CUSHION TA101
	MOLD COMPOUND TA-88-50
C-F-206	FELT WOOL
CCC-C-419	FABRIC DUCK COTTON TY 3
CSD-SH-138	INSULATION FOAM POLYURETHANE VALSALVA
DMS 2072C T2	FILM AL/TEDLAR/NYLON AN16
DP4024	ADHESIVE EPOXY PATCH KIT 1C
DP85193	ADHESIVE EPOXY PATCH KIT 1C
DPA C75-1	CONNECTOR INSERT SILICONE/RUBBER
DPB 3837	FABRIC KELVAR 29
DPB 4-46	FABRIC KELVAR 29
DPKB-1015A	CONNECTOR MALE-MC/ME414-0148
DPM 3883	COATING POLYURETHANE PR1060D
DPM 4875-1	COATING POLYURETHANE PR1568M
DSA 12074C1103	SUNGLASSES AND CASE
E 14653-8A1	RUBBER KALREZ 1046R
E 14653-8A2	RUBBER KALREZ 1046R
E 14653-8B1	RUBBER KALREZ 1046RM
E 14653-8C1	RUBBER KALREZ 1045R
E 14653-8C2	RUBBER KALREZ 1045R
E 14653-8D1	RUBBER KALREZ 1046R2
E 14653-8D2	RUBBER KALREZ 1046R2
E 14653-8E1	RUBBER KALREZ 1046R2M
E 14653-8E2	RUBBER KALREZ 1046R2M
E 14653-B2	RUBBER KALREZ 1046RM
EH32 (82-150)	RUBBER SILICONE NOC
EH32 (83-256)	FASTENER VELCRO NYLON HOOK 65
EH32 (83-288)	FASTENER VELCRO HI-AIR NOMEX HOOK 65 AND LOOP 2000
EH32 (84-147)	FASTENER VELCRO HI-AIR HOOK 65 WITH PS 0372
EH32 (86-285)	WIRE ELEC WITH POLYIMIDE INSULATION
EH32 (86-286)	WIRE ELEC WITH POLYIMIDE INSULATION
EH32 (86-288)	WIRE ELEC WITH POLYIMIDE INSULATION
EI 4053	FABRIC KEVLAR

MSFC-HDBK-527 REV F. 9999942 0006655 0

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
II 4065	CORD KEVLAR
II 4164	FABRIC TEFLON
II-4183	WEBBING DACRON 300LB
IP1664M	SEALANT URETHANE S183026
IPS 37-094	INK CAT-L-INK 50-770
F 508/181	LAMIN PHENOLIC/GLASS
FED L-P-393A	PLASTIC LEXAN 9030 POLYCARBONATE
FED STD 191	FELT NOMEX STYLE 22NX
FED STD 595	COATING 03-BL-51 POLYURETHANE FLAT BLUE
	COATING CPA5197 GREY EPOXY
	COATING CPC3864 WHITE EPOXY
	INK NOC
	LACQUER GREEN COLOR 11105
FED STD 5954	COATING POLYURETHANE BLACK
FFC 0707	COATING CONDUCTIVE INK #703-5-1
FSC 76-1-29	INSULATION FOAM POLYISOCYANURATE FSC17A
	INSULATION FOAM POLYISOCYANURATE FSC18A
FSN 7510-00-2433435	RUBBER BAND NATURAL OR SYNTHETIC SIZE 64
FSN 7530-01-1077383	PAPER GRAPHICS CONTROL ELECTROSTATIC COPY P/N 4036R WITH VERSATEC TYPE H/V80 TONER
FSN 9310-00-0005027	PAPER INDEX LONG GRAIN PULP WOOD FIBER MATERIAL
FSN 9310-00-0005028	PAPER INDEX LONG GRAIN PULP WOOD FIBER MATERIAL
FSN 9310-00-0005030	PAPER INDEX LONG GRAIN PULP WOOD FIBER MATERIAL
G E 47A101715P1	LAMIN EPOXY/GLASS CORDOPREG E293
GC11P409-35-812	CONNECTOR ELECTRICAL
GA100BET	ADHESIVE EPOCAST 8542/38/9242 EPX
GA100BK1	ADHESIVE ADX3103.1 EPOXY
GD 65-00214-1	POTTING COMPOUND EPOXY AP1371 A/B
GD541 & FB117	RUBBER SILICONE RTV 577/9811
GDI-30F	MOLD COMPOUND DAP DC-62
	MOLD COMPOUND DAP FS80/GLASS FILLED
GE TY SEI-GSN3	MOLD COMPOUND NORYL SE-1-GFN3 30
GE171A8299 TYIN	ADHESIVE MPC52 A/B EPOXY
GS-005-70845	PAPER TELETYPEWRITER CARBON
GS-00S-93333	TAPE/DISPENSER VINYL/PVAC
H S 1205 GR A	TEFLON TFE VIRGIN
HC3842	LAMIN EPOXY/GLASS NEMA G11
HAC 90827	TAPE P551B SILICONE
HBO120-105	ADHESIVE ADX3111-1 EPOXY
HBRF55A	ADHESIVE EPON 826/BDE/T6040
HH-C-576	INSULATION CORK
HH-I-536 TY-NMF	INSULATION MICA MUSCOVITE
HK-CWB-1-1	RUBBER FLUOREL FC2170
HK6658 HK6690	COATING PLYTILE R294-151B EPOXY
HMF 133/34	LAMIN FIBERITE T50/934 GRAPHITE WITH ADHESIVE FILM HT424 AND PRIMER
HMS 13-1696	INSULATION FIBERMAT 2539
	INSULATION POLYESTER FIBERMAT 2538
HMS 15-1099	PANEL HONEYCOMB/COATING CTL 15
HMS 15-1099T1C2	COATING CTL15/C15 CAT EPOXY BLACK
HMS 15-2004	INK DYNACURE LETTERING

SPECIFICATION	DESIGNATION
HMS 16-1287T6F1	INSULATION FOAM POLYURETHANE STATHANE G502 SE
HMS 16-2074	LAMIN EPOXY/KEVLAR CE342
	LAMIN HONEYCOMB LEASAT ANTENNA
HMS 2-2103TSJ	WIRE ELEC TEFLON TFE
HMS 2-2103TU	WIRE ELEC FEP WITH POLYIMIDE TAPE
	WIRE ELEC KAPTON FEP POLYIMIDE
HMS 20-1590	LAMIN EPOXY/GLASS CE3201
HMS 20-1654	FABRIC QUARTZ
HMS 20-1658	LAMIN HONEYCOMB LEASAT ANTENNA
HMS 20-2006	INSULATION BLANKET DP50392 TYPE 2 MYLAR/ KAPTON
HMS 20-2075	LAMIN EPOXY/KEVLAR CE342
HP 16-108T1C4	INSULATION FOAM SYNTACTIC EPON 815/KEVLAR
HP 16-108T2C3	INSULATION FOAM SYNTACTIC EPON 815/KEVLAR
HP 16-164	ADHESIVE EA828/DER732/AEP/CABOSIL
HP 16-25	ADHESIVE GOODRICH A1177 A/B EPOXY
HR 608004B	HEATER STRIP/KAPTON 24 AWG
HS 1265	ADHESIVE SCOTCHGRIP 1300
HS 1550	CONNECTOR ELECTRICAL
HS 6074T/B	ADHESIVE CASTALL 1520/E34 EPOXY
HS 798T32	LAMIN EPOXY/GLASS 7781/550/P650M
HSB-2	SOAP IVORY 2OZ
HUG-LAC37-4462	COATING CHEMGLAZE 9922 A/B
III 114000-T2	WEBBING DACRON 900 LB
III 144301-TY5	WEBBING DACRON 800 LB
ILC ST20P623-05	INK BIC MARKING PM DELUX
ILC ST20P623-06	INK BIC MARKING PM DELUX
IP20025	ADHESIVE SCOTCHWELD EC2216 B/A
J-W-1177	WIRE ELEC MAGNET CL 220
J-W-1177/12	WIRE ELEC MAGNET POLYESTER-IMIDE OR POLYESTER-AMIDE-IMIDE CL 180 TYPE H
J-W-1177/13	WIRE ELEC MAGNET CL200 TYPE K POLYESTER
J-W-1177/14	WIRE ELEC MAGNET CL200 TYPE K POLYESTER
J-W-1177/9	WIRE JUMPER NYLESE/PC18M COATED
	WIRE MAGNET NYLON/POLYURETHANE
J-W-1177A	WIRE MAGNET RECTANGULAR POLYVINYL FORMAL COATED CLASS 105 TYPE 2 AND 4
JIS K638 C1503	RUBBER SILICONE SR50
JJ-8-37	INSULATION FOAM POLYIMIDE CHEMLON 701
JT06REIO-355408	CONNECTOR ELECTRICAL
K-SMK-01-2B	PROPELLANT SOLID
KSC-SPEC F-0020	COATING ZINC RICH T1 C1 INORGANIC
KTN 1064	WIRE ELEC KAPTON FEP POLYIMIDE
L 0000R1153	ROD TEFLON/25% GLASS
L 0000R1161	ROD TEFLON/25% GLASS
L-10942	FILTER MEDIA TFE GORE-TEX
L-38-1	LUBE GREASE BRAYCOTE 600
L-I-100 T1	TAPE SCOTCH 853 POLYESTER
LA109-041	COATING PLASMA CHROMIC OXIDE INORGANIC
LAC23-4593	INSULATION FOAM POLYURETHANE HR18
LAC24-4693-0100	ADHESIVE ISOTAC ACRYLIC
LAC24-4760	FILM COPPER/MYLAR
LAC30-4639-0100	ADHESIVE EPIBOND 1210/9615A EPOXY
LAC30-4666	ADHESIVE EPOXY FM73M FILM ON POLYESTER MAT

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
LAC30-4666-0100	ADHESIVE FM73M ON GRAPHITE EPOXY PLATES T50/934
LAC30-4745-0100	ADHESIVE EA956 EPOXY
LAC34-4553	LUBE GREASE BRAYCO 815Z FLUORINATED
LAC34-4554-0200	LUBE GREASE BRAYCOTE 3L-38RP
LAC37-4388-0202	PRINTED WIRING BOARD COPPER CLAD/POLYIMIDE GLASS/CAT-L-INK 50-100 MARKING 1 TO 3 MIL S THICK/URALANE 5075 CONFORMAL COATING 3 TO 5 MILS THICK
LAC37-4462D	COATING CHEMGLAZE II A276/9922 PRIMER
LAC37-4467A	COATING CHEMGLAZE II A276/9922 PRIMER
LAC37-4777-0100	RUBBER SILICONE CV1144-0
LAC40-4394	COATING ACCUMETRIC A105
LAC40-4452	ADHESIVE DC6-1004
LAC40-4647	PRINTED WIRING BOARD COPPER CLAD/POLYIMIDE GLASS/CAT-L-INK 50-100 MARKING 1 TO 3 MIL S THICK/URALANE 5075 CONFORMAL COATING 3 TO 5 MILS THICK
LAC40-4730B	RUBBER SILICONE CV2942
LATUP A/L 23524	LAMIN EPOXY/GLASS RP4002A
LB0130-105	LAMIN F131-21 GLASS/SILICONE
LB0140-004	LUBE DRY VITROLUBE 1220
LB0140-005	LUBE EVERLUBE 620A
	LUBE EVERLUBE 620B1
LCD0607/LCC0618	ADHESIVE CHEMLOK 205 PRIMER WITH CHEMLOK 220 TOPCOAT
LF0400	ADHESIVE FILM LF0400 PYRALUX
LFM 46187	TAPE FLEXITE TGL BLUE ADHESIVE
LMSC 5701803	FOOD RAT/MOUSE
LP 391 T1	PLASTIC PLEXIGLASS GM2064 GRAY
LP-391 T2	PLASTIC ROD METHACRYLATE
LS41164-555	CONNECTOR ELECTRICAL
LS41305-154	CONNECTOR 38108-24-61S
M1192203	TUBING TEFLON TFE HST
M1316F-MF2-5	WIRE ELEC CU/MYLAR/MYLARWRAP
M261-0033-0202	K-6 ALLOY TEST DISCS
M11934/1-10C016	LINER FIBRILOID NOMEX/TFE
M11248/1-025	RUBBER VITON V747-75
M11248/1-026	RUBBER VITON V747-75
M11723-23R2015N	CONNECTOR ELECTRICAL PLUG
MA0105-330	CABLE TIES NOMEX/POLYETHYLENE FC4101
	FABRIC 7878 FIRE/WATER PROOF
	FABRIC NOMEX ARAMID FR P/N E-2
	FABRIC NOMEX K-GUARD CLR#21302
	FABRIC NOMEX RED 5-502 FP/WP
	FABRIC NOMEX-BLUE WITH FC4101-C16
	FABRIC PELLON FR 954
	WEBBING NOMEX 9960 FR
	WEBBING NYLON FIRE/WATER PROOF
	WEBBING STRAP NYLON FIRE/WATERPROOF
	ZIPPER NOMEX/BRASS FIRE/WATER PROOF
MA0105-331	COATING SILICONE BLACK
	FABRIC CERAMIC AB312 SILICONE COATED
MA0106-325C2	COATING DC Q3-6500 SILICONE
MA0106-379	ADHESIVE SYS-SILICA (INORGANIC)
MA0109-316	COATING HI EMITTANCE/WEAR R INORGANIC
MA0150-059	MARKER SLEEVING HT-TMS KYNAR/VITON HS
MA0604-301	INK MARKING FRSI SILICONE
MA0605-303	Z CONFIG ACCEPTION
MA0605-308	FABRIC GAP FILLER
MA0608-303	MULTI-LAYERED INSULATION POLYURETHANE FOAM 416/SUPER KOROPON/RTV 560/HYPALON
MA0609-306	TILE HRSI WITH CC1 AMES COATING
MA0609-308T1	CERAMIC AB312 FABRIC/POLYETHYLENE
MB0-065	INSULATION GLASS FABRIC/ALUMINUM FOIL
MB0105-330	WEBBING NOMEX/COATING FC4101-C-16
MB0110-005	LUBE GREASE BRAYCOTE 3L-38ZN
MB0110-005/T1	LUBE GREASE THERMAL DC340 HS
MB0110-005T1	LUBE GREASE THERMAL DC340 HS
MB0110-005T3	COMPOUND HEAT SINK SILICONE VB
MB0115-010	SEALANT GRAPHITE PYROLITIC
MB0115-018	CARBON GRAPHITE MOLD MECH
MB0115-020	COATING DC Z6070 SILANE
MB0115-021	COATING DC Z6070 SILANE
	COATING HEXAMETHYLDISILAZNE Z6079
	INSULATION AFRSI WITH DISILAZANE Z6079
MB0115-022	COATING SILICONE GLASS/TETRABRN FIL.
MB0115-024	CERAMIC MACOR (INORGANIC)
MB0115-025	INSULATION SIC IMR SI02/GLAZE
MB0115-029	COATING SILICONE GLASS/TETRABRN FIL
MB0115-032	INSULATION S102/SIC/AB312 GLZ (INORGANIC)
MB0120-008	ADHESIVE EA934NA EPOXY
	ADHESIVE EPIBOND 87399 EPOXY
MB0120-023	ADHESIVE NEOPRENE 61015
MB0120-025	ADHESIVE DAPCOTAC 3001
	ADHESIVE NEOPRENE 61015
MB0120-025 ADHESIVE	FASTENER VELCRO NOMEX HAQ 12-1 HOOK WITH 6-1015 NEOPRENE ADHESIVE
MB0120-027T2	ADHESIVE EA9321 EPOXY
MB0120-028	ADHESIVE CHEMLOK 205 PRIMER WITH CHEMLOK 220 TOPCOAT
MB0120-028 PRIMER	FASTENER VELCRO NOMEX HAQ 12-1 HOOK WITH 6-1015 NEOPRENE ADHESIVE
MB0120-031	COATING PM47 PRIMER
MB0120-032	LAMIN EPOXY/PHENOLIC M602
MB0120-037T2	ADHESIVE EA9321 EPOXY
MB0120-040T3	ADHESIVE EPIBOND 8287 EPOXY
MB0120-041	RUBBER SILICONE RTV 102
MB0120-043	INSULATION FOAM POLYURETHANE/FABRIC/REFSET COAT
	INSULATION FOAM URETHANE/LT80/REFSET COATED
MB0120-048	ADHESIVE HT424 EPOXY
MB0120-054	ADHESIVE DC92-018 SILICONE
MB0120-065	COATING REFSET RL4389 CRYO-INSULATION
	INSULATION FOAM/KEVLAR PR1660/SEAL 2030
	SEALANT NEOPRENE DAPCO 2030
MB0120-070 T2C1	FILM BONDING XC453
MB0120-070T1C1	ADHESIVE 453/EC3917 EPOXY FILM
	ADHESIVE AF143/EC3917 EPOXY FILM

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
MB0120-071	ADHESIVE PLASTILOCK 731 EPOXY
MB0120-077	ADHESIVE FOAM AF3018 EPOXY
	ADHESIVE FOAM EA9814 EPOXY
	ADHESIVE METLBOND 6607 FOAM EPOXY
MB0120-078T4	COATING BR 127 EPOXY
MB0120-078T5	ADHESIVE FILM FM24 EPOXY
MB0120-080	ADHESIVE FOAM FM37 MODIFIED EPOXY
MB0120-081T1	ADHESIVE M-BOND 610
MB0120-081T2	ADHESIVE ABLEBOND 463-1 EPOXY/AG FI11
MB0120-084T2	ADHESIVE AE10 EPOXY
MB0120-085	CEMENT FUSED SILICA INORGANIC
MB0120-086	ADHESIVE SCOTCHWELD EC2216 B/A
MB0120-089	ADHESIVE ECCOSIL 4952
MB0120-090	ADHESIVE EC2290 EPOXY
MB0120-096T1	ADHESIVE EPOXY SILVER FILLED K20
MB0120-097	RUBBER SILICONE RTV 3145
MB0120-108	RUBBER SILICONE RTV SWS951
MB0125-002	COATING LAMINAR X500 POLYURETHANE
MB0125-006C1	COATING EPOXY/POLYAMIDE WHITE
MB0125-011	COATING HYPALON 150W-8
MB0125-019	COATING 401 SERIES VELVET POLYESTER
	COATING 401-B2 GRAY
	COATING 401-C10 BLACK
	COATING 401-F1 YELLOW
MB0125-033	COATING A423/T252 EPOXY
MB0125-038	COATING SS4004 SS4004 SILANE
MB0125-040	COATING 643-1-1 POLYURETHANE
	COATING TEMP CONTROL POLYURETHANE/AL
MB0125-043	COATING LAMINATE FLEXIBLE/ALUMINUM/H-FILM
MB0125-044	COATING MOIST BARRIER SIM-LRSI
MB0125-044T2	COATING MOIST BARRIER SIM-HRSI
MB0125-048	SEALANT POLYESTER
MB0125-050	COATING SS4155 SILANE
MB0125-055	COATING 03-BK-29 PRIMER
	COATING 03-GY-62 GRAY OVER MB0125-055 PRIMER
	COATING 03-Y-30 PRIMER
	COATING 463-12-19 EPOXY PRIMER
	COATING 46[illegible]-12-19 PRIMER
	COATING 51 -700/910-704 CATALYST
	COATING 822-326 PRIMER
	COATING 822-327 GRAY 36231 OVER MB0125-055 PRIMER
	COATING 823-311 PRIMER
	COATING 828-310 PRIMER
	COATING SUPER KOROPON 515-700
MB0125-057	COATING HUMISEAL 1B12 ACRYLIC
MB0125-062	ADHESIVE ABLEBOND 783-1 EPOXY
MB0125-063	COATING PYROMARK 2500 HE BLACK
	COATING PYROMARK HE
MB0125-064AT1C3	MULTI-LAYERED INSULATION ALUMINIZED FIBERGLASS/FEP TEFLON TAPE/SILVER/INCONEL/ POLYESTER
MB0125-064T1&2	FILM TEFLON FEP METALIED AL/AG
MB0125-065T1&2	TAPE TEFLON FEP AL/AG Y966 ADHESIVE
MB0125-065T3	TAPE TEFLON FEP SILICONE ADHESIVE
	TAPE TEFLON FEP WITH Y966 TRANSFER ADHESIVE
MB0125-065T3C3	MULTI-LAYERED INSULATION ALUMINIZED FIBERGLASS/FEP TEFLON TAPE/SILVER/INCONEL/ POLYESTER
MB0125-066T1C3	FILM KAPTON ALUMINIZED
MB0125-067T1&2	TAPE KAPTON AL/AU WITH Y966 ADHESIVE
MB0125-067T3	TAPE SCOTCH Y966 ACRYLIC TRANSFER
MB0125-069	COATING DC 92-007 SILICONE
MB0125-070	COATING 02-GY-3 EPOXY
	COATING 02-GY-3 WITH ARAMID LAMIN
	COATING 02-GY-3 WITH KEVLAR LAMIN
MB0125-071	TAPE POLYESTER 415/ACRYLIC ADHESIVE
MB0125-072	COATING SOLITHANE 113/300
MB0125-074	COATING EPOXY AMINE
MB0125-075	COATING TEFLON INFUSED
	RUBBER SILICONE E2038 HI-DAMP
	RUBBER SILICONE E2041 HI-DAMP
MB0125-078	COATING LATEX FRL3 FLAME RETARDANT
	INSULATION FOAM PDL4034/COATED WITH FRL
MB0125-079	COATING SLIP RESISTANT POLYURETHANE
MB0125-080	COATING CHEMGLAZE II A276
MB0125-084	COATING CHEMGLAZE 9924 A/B
MB0125-086	COATING KRYLON 1301 CLEAR
MB0125-087	COATING DAPCOTAC 3300TH ADHESIVE
MB0130-001	LAMIN EPOXY/GRAPHITE
MB0130-004C1T6	LAMIN PHENOLIC/GLASS F508 VOLAN A/7781
MB0130-004T6C2	LAMIN PHENOLIC 2210/A1100/1581
MB0130-0104T8	DUCT GLASS/POLYIMIDE 7781/F178
MB0130-014	CORE HRP/HFT GLASS/PHENOLIC HC
MB0130-024	FILM TEDLAR 200BG30 PVF
MB0130-025	ADHESIVE XR5038 EPOXY
MB0130-027	RUBBER BUTYL
MB0130-027T1	RUBBER BUTYL
MB0130-033	INSULATION ABLATIVE EPOXY/POLYIMIDE 183K2
MB0130-052	TEFLON FEP
MB0130-068	FABRIC GAP FILLER
	RUBBER SILICONE RTV 602 CLEAR
MB0130-077	INSULATION FOAM BX250 VARIOUS RATIO POLYURETHANE
MB0130-079	INSULATION FOAM 402 POLYURETHANE
MB0130-081	LAMIN POLYIMIDE/GLASS
MB0130-083	FLUOROCARBON RL-3540 GUM STOCK
MB0130-084T2	RUBBER FLUOREL 1062
	SPONGE FLUOREL RL2060
MB0130-085	RUBBER SILICONE RTV 566
MB0130-087	LAMIN EPOXY/GRAPHITE 3501/AS
	LAMIN EPOXY/GRAPHITE 5208/T300
MB0130-087T3C4	CONFIG SEE 06475/05325
	LAMIN EPOXY/GRAPHITE
MB0130-099	SPONGE RUBBER SILICONE PD200-16 SILICONE
MB0130-101T2	LAMIN EPOXY/BORON SP296
MB0130-102	RUBBER SILICONE DC93-072
MB0130-104AT8B	LAMIN POLYIMIDE/GLASS

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
MBO130-104T8	LAMIN POLYIMIDE/GLASS
MBO130-104T8B	DUCT GLASS/POLYIMIDE 7781/F178
	LAMIN POLYIMIDE/GLASS CP2252/7781
	LAMIN POLYIMIDE/RESIN X PLY
MBO130-105	CONFIG NYLON VELCRO/COTTON
	CONFIG NYLON VELCRO/COTTON COF
	LAMIN EPOXY/GLASS
	LAMIN EPOXY/GLASS F164-1/7781
	LAMIN EPOXY/GLASS F164/7781
MBO130-105C1GFR	LAMIN EPOXY/GLASS CE9010
MBO130-105T3	LAMIN EPOXY/GLASS CE9010/120
MBO130-105T3B	LAMIN EPOXY/GLASS F164/7781
MBO130-105T3C1	INSULATION LAMINATE E7023-1581
	LAMIN EPOXY/GLASS
MBO130-105T8B	LAMIN EPOXY/KEVLAR CE9010/7781
MBO130-105T8BC1	LAMIN EPOXY/GLASS CE9020/7781
	LAMIN EPOXY/GLASS E720E/7581 FR
	LAMIN EPOXY/GLASS F164-1
	LAMIN F161-173G/7781 EPOXY/GLASS
MBO130-105T8C1	LAMIN EPOXY/GLASS F164-1/7781
MBO130-105T8FR	RUBBER SILICONE RTV 560 EPOXY/GLASS
MBO130-105T8GP	LAMIN EPOXY/GLASS
MBO130-106	ADHESIVE PR1710-1711 VITON
MBO130-107T1	RUBBER SILICONE DC93-076
MBO130-119	FELT NOMEX/SILICONE COATED
	RUBBER SILICONE RTV 560 EPOXY/GLASS
MBO130-119T1	RUBBER SILICONE RTV 511/SS4155
MBO130-119T1&3	RUBBER SILICONE RTV 511/577
MBO130-119T2	RUBBER SILICONE RTV 560
MBO130-119T2+3	RUBBER SILICONE RTV 560/577
MBO130-119T3	RUBBER SILICONE RTV 577/T12
MBO130-125	LAMIN POLYIMIDE HI3003
	LAMIN POLYIMIDE/GLASS
	LAMIN POLYIMIDE/GLASS HI3000
	LAMIN POLYIMIDE/GLASS MICAPAK PG402T
MBO130-127	LAMIN DUCT 02GY3 TC URETHANE 17875
MBO130-127T3	COATING 02-GY-3 WITH ARAMID LAMIN
	COATING 02-GY-3 WITH KEVLAR LAMIN
	DUCT E-720-E FR/120/MBO125-070
	LAMIN EPOXY/ARAMID F164
	LAMIN EPOXY/GLASS CE9010/181 KEVLAR 49
	LAMIN EPOXY/GLASS CE9020/KEVLAR 49
	LAMIN EPOXY/KEVLAR E720E FR 49-120
	LAMIN EPOXY/KEVLAR F164/120 KEVLAR 49
	LAMIN F164/181 KEVLAR-49
MBO130-127T8	LAMIN EPOXY/ARAMID
	LAMIN EPOXY/KEVLAR F164-1/181
MBO130-128T1	INSULATION FOAM KOROPON SUPER/RTV560/ HYPOLIN
	INSULATION FOAM POLYURETHANE FR6704/EC2241 4PCF
	MULTI-LAYERED INSULATION POLYURETHANE FOAM 416/SUPER KOROPON/RTV 560/HYPALON
MBO130-128T2	FOAM POLYURETHANE LAST-A-FOAM
MBO130-130	SEALANT POLYURETHANE PR1660

SPECIFICATION	DESIGNATION
MBO130-131	SEALANT CYANOSILICONE PRP711
MBO130-132	RUBBER EPR AF-E411
MBO130-133T2	INSULATION FOAM POLYURETHANE 711
	INSULATION FOAM POLYURETHANE/FABRIC/REFSET COAT
MBO130-134	LAMIN FIBERFRAX T30LR (INORGANIC)
MBO130-135	CONFIG SEE 06475/05325
MBO130-136	INSULATION FOAM POLYURETHANE/FABRIC/REFSET COAT
	INSULATION FOAM/KEVLAR PR1660/SEAL 2030
	SEALANT POLYURETHANE PRP1600
MBO130-137/T2	ADHESIVE ECCOFOAM FPH12-4H
MBO130-140	VESPEL SP21
MBO130-140T6	LAMIN POLYIMIDE/GLASS F174
MBO130-142	VESPEL SP21
MBO130-142T1-11	VESPEL SP21
MBO130-143	INSULATION FOAM EPOXY SYNTACTIC MODIFIED
MBO130-144	RUBBER SILICONE RTV 142
MBO130-148	CORE HRP/HFT GLASS/PHENOLIC HC
MBO130-149	INSULATION FOAM PDL4034-2.5S/ENSHROUDED IN METAL FOIL
	INSULATION FOAM PDL4034-2.5S/RL4389/TAPE
	INSULATION FOAM PDL4034/COATED WITH FRL
	INSULATION FOAM/KEVLAR PR1660/SEAL 2030
MBO130-150	SPONGE RUBBER SILICONE ADHESIVE PS
MBO130-152T1C1	LAMIN GRAPHITE/POLYIMIDE
MBO130-154	KEL-F 800 MEK/SPRAY
MBO130-160T2C1	LAMIN EPOXY/GRAPHITE
MBO130-169	RUBBER SILICONE SMC1050
MBO130-171	TUBING FEP TEFLON
MBO130-174	CORE ARAMID PHENOLIC COATED GLASS FILLED
MBO130-175	COATING SILICONE GLASS/TETRABRN FIL
	FABRIC CERAMIC AB312 SILICONE COATED
MBO135-002	FABRIC GLASS/TFE COATED
MBO135-009	FABRIC GLASS FOR PLASTIC LAMIN
MBO135-018T2	FABRIC GLASS/PTFE COATED VM3033
MBO135-020	TAPE MYSTIK 7455 ADHESIVE
	TAPE SCOTCH 363 REFLECTIVE
MBO135-021	FABRIC NYLON
MBO135-024	INSULATION SILICONE THERMAL
	INSULATION TG15000/MYLAR/FEP TAPE
	INSULATION TG15000/SCOTCH 853 TAPE
	INSULATION TG15000/SILICONE/GLASS BINDER
	INSULATION TG15000/TI/TAPE 853/KAP
MBO135-024T1	INSULATION GLASS/SILICONE M-S-AA
	INSULATION TG15000/SILICONE/GLASS BINDER
MBO135-024T1C1	INSULATION TG15000/MYLAR/L-T-80 TAPE
MBO135-024T2	INSULATION TG15000/SILICONE/GLASS BINDER
MBO135-027	FABRIC X-389-7 BETA/GLASS/TFE
MBO135-027F	FABRIC TEFLON T9362/TFE COATED
MBO135-027FMGF	FABRIC TEFLON/COATED BETA CLOTH
MBO135-028	FABRIC SILICONE/CR/PTFE V3037
MBO135-029	THREAD QUARTZ TFE COATED
MBO135-02H	INSULATION TG15000/MYLAR/L-T-80 TAPE
MBO135-030	ROPE SILICA SS1404 (INORGANIC)

MSFC-HDBK-527 REV F 9999942 0006659 8

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
MB0135-031	INSULATION FLEX ALUMINA SILICATE
MB0135-031T24	INSULATION FLEX ALUMINA SILICATE
MB0135-031T8	INSULATION FLEX ALUMINA SILICATE
MB0135-034T1	FILM POLYESTER ALUMINIZED
	MULTI-LAYERED INSULATION ALUMINIZED FIBERGLASS/FEP TEFLON TAPE/SILVER/INCONEL/ POLYESTER
MB0135-035	LACING TAPE HT-30 LOC B NOMEX
	LACING TAPE NOMEX RD1251Z
	LACING TAPE NOMEX/VITON 1342V
MB0135-035T1	LACING TAPE HT-30 LOC B NOMEX
	LACING TAPE HT-30-TVS NOMEX
	LACING TAPE NOMEX
	LACING TAPE NOMEX/VITON 1342V
	LACING TAPE NOMEX/VITON 1342VC
MB0135-035T2	LACING TAPE HT-30 LOC B NOMEX
	LACING TAPE NOMEX 1342G
MB0135-036T3	FILM POLYIMIDE ALUMINIZED
MB0135-038	FILM KAPTON GOLDIZED
MB0135-038T1C4	FILM NM50-49 KAPTON GOLDIZED
MB0135-038T2	INSULATION BLANKET KAPTON/DACRON/NOMEX
	MULTI-LAYERED INSULATION DACRON NET B4A/ GOLDIZED KAPTON/TG15000 SILICONE GLASS/ G411660
MB0135-038T2C1	MULTI-LAYERED INSULATION GOLDIZED KAPTON/ DACRON MESH/NOMEX
MB0135-041T5	MULTI-LAYERED INSULATION DACRON NET B4A/ GOLDIZED KAPTON/TG15000 SILICONE GLASS/ G411660
MB0135-042	INSULATION BLANKET KAPTON/DACRON/NOMEX
	MULTI-LAYERED INSULATION DACRON NET B4A/ GOLDIZED KAPTON/TG15000 SILICONE GLASS/ G411660
	MULTI-LAYERED INSULATION DACRON NET B4A/ TG15000 SILICONE GLASS/KAPTON/PBI
	MULTI-LAYERED INSULATION GOLDIZED KAPTON/ DACRON MESH/NOMEX
	MULTI-LAYERED INSULATION KAPTON/ALUMINUM/ TG15000 SILICONE GLASS/DACRON NET B4A/PBI
MB0135-042/084	MULTI-LAYERED INSULATION DACRON NET B4A/ POLYBENZIMIDAZOLE/TG15000 SILICONE GLASS/ TAPE G411970 ALUMINUM/KAPTON ADHESIVE
MB0135-042T2C1	MULTI-LAYERED INSULATION DACRON NET B4A/ ALUMINUZED KAPTON/PBI/ALUMINIZED KAPTON RIPSTOP
MB0135-042T2GA	MULTI-LAYERED INSULATION DACRON NET B4A/ KAPTON/ALUMINUM/PBI
MB0135-047	INSULATION TG15000/MYLAR/FEP TAPE
	INSULATION TG15000/MYLAR/L-T-80 TAPE
	INSULATION TG15000/SILICONE/GLASS BINDER
	INSULATION TG15000/TI/TAPE 853/KAP
MB0135-047T4	INSULATION TG15000/SILICONE/GLASS BINDER
	MULTI-LAYERED INSULATION HITCO TG15000/ G134600 GOLDIZED KAPTON
MB0135-047T5	MULTI-LAYERED INSULATION DACRON NET B4A/ POLYBENZIMIDAZOLE/TG15000 SILICONE GLASS/ TAPE G411970 ALUMINUM/KAPTON ADHESIVE
	MULTI-LAYERED INSULATION DACRON NET B4A/ TG15000 SILICONE GLASS/KAPTON/PBI
	MULTI-LAYERED INSULATION KAPTON/ALUMINUM/ TG15000 SILICONE GLASS/DACRON NET B4A/PBI
MB0135-048T2	INSULATION BLANKET KAPTON/DACRON/NOMEX
	MULTI-LAYERED INSULATION DACRON NET B4A/ GOLDIZED KAPTON/TG15000 SILICONE GLASS/ G411660
	MULTI-LAYERED INSULATION GOLDIZED KAPTON/ DACRON MESH/NOMEX
	MULTI-LAYERED INSULATION HITCO TG15000/ G134600 GOLDIZED KAPTON
	TAPE G411660 5 MIL KAPTON WITH VACUUM DEPOSITED ALUMINUM
MB0135-048T3	TAPE G411660 5 MIL KAPTON WITH VACUUM DEPOSITED ALUMINUM
MB0135-050	TAPE 2345-1 KAPTON/SILICONE
MB0135-050T1	TAPE 2345-1 KAPTON/SILICONE
MB0135-050T2	TAPE G402600 VACUUM DEPOSITED GOLD 1 MIL KAPTON WITH MYSTIC 7361 SILICONE ADHESIVE
MB0135-050T3	TAPE POLYIMIDE T966
MB0135-050T4	TAPE POLYIMIDE AU/AL PS ADHESIVE
MB0135-050T5	TAPE NM53-57 KAPTON/AL ORGANIC COATED
	TAPE POLYIMIDE AU/AL PS ADHESIVE
	TAPE POLYIMIDE T966
MB0135-051T2	FELT NOMEX NON-WOVEN
MB0135-051T2C1	FELT NOMEX S2335 NRB/Z
MB0135-052	INSULATION PILE FIBROUS (INORGANIC)
MB0135-053	FABRIC KELVAR 29
	INSULATION FOAM POLYURETHANE/FABRIC/REFSET COAT
	TUBING POLYIMIDE ARAMID
MB0135-054	FABRIC HT-46-XX ARAMID WOVEN
	FABRIC NOMEX HT-49
	GASKET MATERIAL RUBBER SILICONE/NOMEX
	GASKET SILICONE NOMEX HT 46-45
MB0135-055	FABRIC HT-2002 ARAMID/KNIT MESH
	FABRIC SILICONE RUBBER/ARAMID
	GASKET MATERIAL RUBBER SILICONE/NOMEX
MB0135-056	FELT NOMEX/DC92-007 SILICONE COATED
MB0135-058T1	FELT NOMEX/SILICONE COATED
MB0135-059	TAPE G143902 TFE/GLASS/GOLD/SILICONE ADHESIVE
MB0135-059ALL	TAPE SCOTCH 5451
MB0135-059T1	TAPE G143902 TFE/GLASS/GOLD/SILICONE ADHESIVE
MB0135-060	FABRIC NYLON MESH NON-MELTING
MB0135-061T11C2	TAPE G40700 KAPTON/GOLD ADHESIVE
MB0135-062	MULTI-LAYERED INSULATION ALUMINIZED FIBERGLASS/FEP TEFLON TAPE/SILVER/INCONEL/ POLYESTER
	TAPE MYSTIK 7455 ADHESIVE

MSFC-HDBK-527 REV F 9999942 0006660 4

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
MB0135-062	TAPE SCOTCH YR364 ALUMINUM GLASS WITH SILICONE ADHESIVE
MB0135-063	TAPE G404200/G404202TFE/AG/SILICONE ADHESIVE
MB0135-063T1	TAPE G401900 5 MIL TYPE A TEFLON WITH VAC DEPOSITED SILVER AND INCONEL WITH 966 ACRYLIC ADHESIVE
MB0135-063T2	TAPE G404200/G404202TFE/AG/SILICONE ADHESIVE
MB0135-065	CERAMIC AB312 FABRIC/POLYETHYLENE
MB0135-065T1	FABRIC CERAMIC AB312 WITH Z6070
MB0135-065T3	FABRIC GAP FILLER
MB0135-066	CERAMIC BRAID SLEEVING SF2600
	FABRIC CERAMIC AB312 SILICONE COATED
MB0135-066/CTD	CERAMIC AB312 FABRIC/ACRYLIC/FC723
	CERAMIC AB312 FABRIC/POLYSULFONE/FC723
MB0135-067	INSULATION SAFFIL ALUMINA HT MAT
MB0135-071	FABRIC/TAPE 581 QUARTZ (INORGANIC)
MB0135-072	THREAD QUARTZ TFE COATED
MB0135-075	THREAD NYLON
MB0135-079 3	TAPE G148020 AL/POLY/NOMEX/ADHESIVE
MB0135-079T1	TAPE G148020 AL/POLY/NOMEX/ADHESIVE
MB0135-079T2	FILM G402474 VAL/POLYIMIDE
MB0135-082T1	INSULATION MATERIAL 550-02 QUARTZ FIBER
MB0135-083	FILM NM50-13 KAPTON/NOMEX
	MULTI-LAYERED INSULATION DACRON NET B4A/ ALUMINUZED KAPTON/PBI/ALUMINIZED KAPTON RIPSTOP
	MULTI-LAYERED INSULATION DACRON NET B4A/ KAPTON/ALUMINUM/PBI
	MULTI-LAYERED INSULATION DACRON NET B4A/ TG15000 SILICONE GLASS/KAPTON/PBI
	MULTI-LAYERED INSULATION KAPTON/ALUMINUM/ TG15000 SILICONE GLASS/DACRON NET B4A/PBI
	TAPE AL/KAPTON/ORGANIC COATED
	TAPE G411600 AL-KAPTON/ORGANIC COATED
MB0135-084	MULTI-LAYERED INSULATION DACRON NET B4A/ POLYBENZIMIDAZOLE/TG15000 SILICONE GLASS/
	TAPE G411970 ALUMINUM/KAPTON ADHESIVE
MB0135-084C1T2	TAPE G411970 ALUMINUM/KAPTON/ADHESIVE
MB0135-084T1C2	FILM G412020 KAPTON/ALUMINUM/ORGANIC COATED
	FILM NM54-15 KAPTON AL/ORGANIC COATED
	TAPE G411520 2 MILSRÍ KAPTON VACUUM DEPOSITED ALUMINUM WITH ACRYLIC OVERCOAT
MB0135-084T2C1	MULTI-LAYERED INSULATION DACRON NET B4A/ ALUMINUZED KAPTON/PBI/ALUMINIZED KAPTON RIPSTOP
	MULTI-LAYERED INSULATION DACRON NET B4A/ TG15000 SILICONE GLASS/KAPTON/PBI
MB0135-084T2GA	MULTI-LAYERED INSULATION DACRON NET B4A/ KAPTON/ALUMINUM/PBI
MB0135-085	INSULATION AFRSI WITH DISILAZANE Z6079
	INSULATION AFRSI WITH SILANE Z6070
	INSULATION BLANKET SILICONE/S-GLASS/Q-FELT

SPECIFICATION	DESIGNATION
MB0135-088	THREAD GLASS FIBER INORGANIC
MB0135-133T2	INSULATION FOAM POLYURETHANE/AL TAPE L-T-80
	INSULATION FOAM URETHANE/LT80/REFSET COATED
MB0135-135	CORE HRN-10 NOMEX/PHENOLIC
MB0135-027GF	FABRIC TEFLON/COATED BETA CLOTH
MB0140-001	SEALANT LOX-SAFE
MB0140-005	LUBE GREASE BRAYCO 640AC
	LUBE GREASE KRYTOX 240AC
MB0140-005A	LUBE GREASE BRAYCO 640AC
MB0140-008	LUBE OIL SILICONE F6-1101
MB0140-009	LUBE DRY DICRONITE DL5
MB0140-010BT1	LUBE GREASE BRAYCO 815Z FLUORINATED
MB0140-010T1	LUBE GREASE BRAYCO 815Z FLUORINATED
MB0140-010T2	LUBE GREASE BRAYCOTE 3L-38RP
	LUBE GREASE BRAYCOTE 601
MB0150-005	LUBE GREASE KRYTOX 240AC
MB0150-025C12&3	TUBING TEFLON TFE HST
MB0150-025C4	TUBING TFE/FEP TYPE WFT
MB0150-025C5	TUBING TEFLON FEP HST
MB0150-035	WIRE ELEC TFE/ML ENAMEL
MB0150-048	WIRE ELEC FEP/POLYIMIDE TAPE
MB0150-051	WIRE ELEC FEP WITH POLYIMIDE TAPE
MB0150-053	CABLE COAXIAL TFE/FEP
MB0150-056	CABLE COAXIAL TFE/FEP
MB0150-057	CABLE COAXIAL TFE/FEP
MB0150-059T1	TUBING POLYVINYLFLOURIDE K46 HS
MB0150-060	HALAR E-CTFE
	TUBING BEN-HAR EXPANDO
MB0150-061	WIRE ELEC FEP/POLYIMIDE TAPE
	WIRE ELEC TFE/ML ENAMEL
MB0150-062	WIRE ELEC TEFLON PFA
MB0150-064T1	TUBING KYNAR CONVOLUTED BLACK
	TUBING KYNAR RT1150 CONVOLUTED
MB0150-064T2B	TUBING KYNAR CONVOLUTED/SS COVR
MB0150-066	WIRE ELEC RAYCHEM 44 ALL GAGES
MB0150-066/12	WIRE ELEC RAYCHEM 44 ALL GAGES
MB0160-046	THREAD CRES 304 MF-A1 28/61/5Z
MB0190-001	LABEL IDENTIFICATION ASSEMBLY ACRYLIC ADHESIVE/AL
MB0190-003T1	INK 73X
MB0190-003T2	INK CAT-L-INK 50-700R/9
	INK WORNOW 50-100R/9 WHITE
MB0190-006	INK WORNOWINK M-O-N/CAT A
MC-5X	FABRIC COTTON BLUE MOUNTAIN
MC-61024	LUBE GREASE TRIBOLUBE 10
MC-8299-01	LACING TAPE DACRON
MC250-0002	RUBBER VITON FLUID RESISTANT
MC276-0004	VESPEL SP21
MC276-0010	VESPEL SP21
MC276-0012	VESPEL SP21
MC276-0032	KYNAR 740
MC284-0389	TEFLON FEP
MC284-0391	COATING 851-224 GREEN/850-204 GREEN

MSFC-HDBK-527 REV F 9999942 0006661 6

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
MC284-0395	KEL-F CTFE UNPLASTICIZED
	VESPEL SP21
MC284-0396	VESPEL SP21
MC284-0397	VESPEL SP21
MC284-0429	MAGNET 2V PERMENDUR
MC287-00540001	ADHESIVE P82 C
MC364-0006	TILE SILICA LI0036/OVERCOATED
	TILE SILICA LI0050/OVERCOATED
MC409-0014	INSULATION WIRE SILICONE J-SIL39013
MC409-0126	COATING PC 29/29M POLYURETHANE
MC414-0613-0004	CONNECTOR PC BOARD 10-398050-1P
MC430-84	FABRIC COTTON BLUE MOUNTAIN
MC432-0205	TUBING KORVEX TFE HS
MC454-0066-0027	INSULATION PLENCO 1512 ALKYD/GLASS
MC476-0028	ADHESIVE POLYFREEZE P146 EPOXY
MC621-0043	INK 8447 BLACK
MC6346-01	MOLD COMPOUND C2175 EPOXY
MC7609-01	ADHESIVE P75 FOAM
MC7768-01	POTTING COMPOUND URETHANE
MC7935-01	COATING EPOXY POLYIMIDE
	COATING EPOXY POLYIMIDE/PRIMER
MC7994-03	COATING SILICONE/PRIMER
MC3006-01	COATING SILICONE/PRIMER
MC3006-101	COATING DC 1201 CLEAR SILICONE
MC3017-01	POLYIMIDE-CU
MC3024-1	LAMIN EPOXY/GLASS FR4
MC3025-01	LAMIN EPOXY/GLASS STRIPPED
MC3257-01	LAMIN EPOXY/GLASS
MC3296-09T2	ADHESIVE SE881/CA2
MC3296-09T3	ADHESIVE SE881/CA2
MC3296-09T4	ADHESIVE SE881/CA2
MC3296-10T2	ADHESIVE SE881/CA2
MCR 7583	TAPE SCOTCHCAL 5690 VINYL
MD411-4010	STRAP ELEC AL KAPTON/PBI
MD920-12-4	WIRE ELEC WITH POLYIMIDE INSULATION
MD920-20-6	WIRE ELEC WITH POLYIMIDE INSULATION
MD920-22-1	WIRE ELEC WITH POLYIMIDE INSULATION
MD920-8	WIRE ELEC WITH POLYIMIDE INSULATION
MD921-20	WIRE ELEC POLYIMIDE INSULATION
MDA-151ET	LAMIN PHENOLIC/COTTON TYPE FBM
MDM1892	TAPE MYSTIK 7001 GLASS/SILICONE ADHESIVE
MDM3279	ADHESIVE SCOTCHWELD EC2216 B/A
MDTSCO 9M03513	LUBE GREASE BRAYCOTE 601
ME127-0012-0016	CLAMP SILICONE/GLASS
ME127-0028-7XXX	CLAMP SILICONE/GLASS
ME127-0071-3016	CLAMP CUSHION SILICONE/FIBERGLASS CL 3B GR 60
ME171-0005-0001	NYLON 6/6 ZYTEL 101
ME171-0005-0003	NYLON 6/6 ZYTEL 101
ME171-0005-0004	NYLON 6/6 ZYTEL 101
ME171-0005-0005	NYLON 6/6 ZYTEL 101
ME171-0005-0007	NYLON 6/6 ZYTEL 101
ME171-0005-0008	NYLON 6/6 ZYTEL 101
ME171-0005-0009	NYLON 6/6 ZYTEL 101
ME251-0011	RUBBER VITON FLUID RESISTANT

SPECIFICATION	DESIGNATION
ME261-0033	K-6 ALLOY TEST DISCS
ME261-0033-0202	K-6 ALLOY TEST DISCS
ME261-0033-0204	K-6 ALLOY TEST DISCS
ME261-0033-0206	K-6 ALLOY TEST DISCS
ME261-0033-0208	K-6 ALLOY TEST DISCS
ME261-0033-0212	K-6 ALLOY TEST DISCS
ME261-0033-202	K-6 ALLOY TEST DISCS
ME261-0033-206	K-6 ALLOY TEST DISCS
ME261-00330202	K-6 ALLOY TEST DISCS
ME261-0033T3	K-6 ALLOY TEST DISCS
ME261-0045	COATING 850-204/851-214 GREEN
ME276-0032	KYNAR 460
ME413-0038	RUBBER SILICONE 24037 CARBON/FILLED
ME413-0041	RUBBER NEOPRENE NS6022
ME414-0235	MOLD COMPOUND EPIALL 1908
ME414-0611-0002	CONNECTOR ELECTRICAL
ME416-0031	KYNAR MELTABLE PIGMENTED BLUE
	KYNAR MELTABLE PIGMENTED RED
	KYNAR MELTABLE PIGMENTED YELLOW
ME416-0033	MOLD COMPOUND POLYETHYLENE THERMAL ST
MIL-1-2305315	TUBING FP301 INSULTITE HST
MIL-1-3158TYS	CORD FIBERGLASS RESIN TREATED
MIL-174C1GRB	SILICA DYNASIL 5000 FUSED INORGANIC
MIL-2305315	TUBING POLYOLEFIN RNF100
MIL-23699	LUBE OIL SYNTHETIC (DIESTER)
MIL-9-55110	PRINTED WIRING BOARD COPPER CLAD/POLYIMIDE GLASS/CAT-L-INK 50-100 MARKING 1 TO 3 MIL S THICK/URALANE 5075 CONFORMAL COATING 3 TO 5 MILS THICK
MIL-A-21366	ADHESIVE EC1357 NEOPRENE CEMENT
MIL-A-25463	ADHESIVE METLBOND 328
MIL-A-25463T1/2	ADHESIVE FILM FM123-2LVC EPOXY
MIL-A-25463T2/2	ADHESIVE FILM FM300 EPOXY
MIL-A-46050	ADHESIVE EASTMAN 901
	ADHESIVE RAPIDSET BLUE EPOXY
	ADHESIVE SUPERBONDER 496 ACRYLIC
MIL-A-46050CT1	ADHESIVE PERMABOND 200
MIL-A-46106	RUBBER SILICONE RTV 108
	RUBBER SILICONE RTV 162
MIL-A-46106AT1	RUBBER SILASTIC RTV 732
MIL-A-46146	RUBBER SILICONE RTV 162
	RUBBER SILICONE RTV 168
MIL-A-46146T1	RUBBER SILICONE RTV 3145
MIL-A-46864	ADHESIVE EPOXY
	ADHESIVE SCOTCHWELD EC2216 B/A
MIL-A-47089	FABRIC TECKNIT 72-08116AG FILL
MIL-A-7021C1	GASKET MAIL ASBESTOS/RUBBER
MIL-A-8623	ADHESIVE EA940 EPOXY
	ADHESIVE SCOTCHWELD 3520 B/A
MIL-A-907	ADHESIVE LOCTITE E/LOCTITE T PRIMER
MIL-B-121E	LINER FIBRILOID NOMEX/TFE
MIL-B-131FC2	RUBBER EPR MARVEL SEAL 1312
MIL-B-22191T3	FILM NYLON
MIL-B-81705T11	BAG POLYETHYLENE RCAS 1200
MIL-B-81705T2	FILM POLYETHYLENE

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
MIL-C 27500/16	WIRE ELEC KAPTON TAPE/GLASS TUBE
MIL-C-0038999	CONNECTOR ELECTRICAL 73E
MIL-C-005015	CONNECTOR ELECT SILICONE RUBBER/CERAMIC
MIL-C-12369F	FABRIC NYLON/ACHESON +500
	FABRIC NYLON/VITON
MIL-C-13924C1	COATING BLACK OXIDE (INORGANIC)
MIL-C-16173G2&3	COATING CORROSION PREVENTIVE
MIL-C-16173G23	CLEANER BRAYCOTE 137
MIL-C-17	CABLE COAX RG179 PTFE CORE FEP JACKET
	SILVER COATED COPPER
	CABLE COAX RG6178 PTFE CORE FEP JACKET
	SILVER COATED COPPER
MIL-C-17/176B	CABLE 77 OHM TWINAX
MIL-C-17/60	CABLE ELECTRICAL 07145 AG COATED CU WITH
	TEFLON AND ALUMINIZED MYLAR
MIL-C-17/RG-58	WIRE ELEC PVC-A
MIL-C-175	CABLE 77 OHM TWINAX
MIL-C-17E12814	CABLE COAX RG142 PTFE CORE FEP JACKET
	SILVER COATED COPPER
MIL-C-19459	COATING CORROSION INHIBITNG COMPOUND
MIL-C-20079G YARN	FABRIC THERMOGLASS HEAT TREATED
MIL-C-22750	COATING EPOXY POLYAMIDE RED 11105
	COATING POLYAMIDE RED 11136 EPOXY
	COATING POLYIMIDE BLACK 37038 EPOXY
MIL-C-22750C1T3	COATING BLACK 37038 POLYAMIDE EPOXY
	COATING GRAY 36231 POLYAMIDE EPOXY
MIL-C-22750T2	COATING 453-4-BLUE POLYAMIDE SEMI-GLOSS
	EPOXY 212
MIL-C-22750T3C1	COATING EPOXY/POLYAMIDE
MIL-C-22751	COATING PLYTILE R294-151B EPOXY
MIL-C-24308	CONNECTOR ELECTRICAL 22541
MIL-C-27500	WIRE ELEC RAYCHEM 44/KAPTON
	WIRE ELEC TEFLON TFE
	WIRE ELEC WITH FIBERGLASS SLEEVE
MIL-C-27500/16	WIRE ELEC RAYCHEM 44 MYLAR/KAPTON
MIL-C-27500/20	WIRE ELEC POLYIMIDE INSULATION
MIL-C-27500/22	WIRE ELEC FEP WITH POLYIMIDE TAPE
MIL-C-27599	RECEPTACLE MS27503Y8E-35P
MIL-C-27617CT3	LUBE GREASE BRAYCOTE 805B2
MIL-C-28748	CONNECTOR RECTANGULAR RACK AND PANEL P/N
	MM22G5-44SK2H AND P/N MMDIP2265-44SL2L
MIL-C-28804	CONNECTOR ELECTRICAL
MIL-C-38351T1C1	FASTENER VELCRO NOMEX HAQ 12-2-200 NYLON
	LOOP
MIL-C-38351T2C1	CURTAIN HYGIENE CLOSURE
	FABRIC AROMATIC/NON-MELTING
	FABRIC HT-90-40 NOMEX
	FABRIC NOMEX COATED WITH SCOTCHGARD FC4101
	FASTENER VELCRO NOMEX HAQ 12-1-200 NYLON
	HOOK
MIL-C-3851T2C1	FABRIC NOMEX/VELCRO/FC4101
MIL-C-3899	RECEPTACLE MS27503Y8E-35P
MIL-C-38999	CONNECTOR ELECTRIC 84450
	CONNECTOR ELECTRIC G & HV
	CONNECTOR ELECTRICAL

SPECIFICATION	DESIGNATION
MIL-C-38999	CONNECTOR ELECTRICAL 18-32 #4
	CONNECTOR ELECTRICAL 18-32P #1
	CONNECTOR ELECTRICAL 97E
MIL-C-39012	CONNECTOR ELECTRICAL
MIL-C-3953	FABRIC DUCK NYLON CLOTH
MIL-C-43006	FABRIC NYLON/PVC HERCULITE 20
MIL-C-43006BT1	FABRIC FACILON 1814 PVC BLUE
MIL-C-43006BT2	FABRIC HERCULITE 80 NYLON
MIL-C-43006C	FABRIC FACILON NYLON/VINYL BLU
MIL-C-5015	CONNECTOR ELECTRICAL
MIL-C-55302	CONNECTOR PLASTIC WTB56SAD11SY-17
MIL-C-55302/59	CONNECTOR PC BOARD WTB90PR-7SY-X/WTB90SED-
	9SY-X
MIL-C-554	DYE RED
MIL-C-5541	COATING CONVERSION CHROMATE
MIL-C-5646T1	FABRIC COTTON NATURAL
MIL-C-5651CT1	CORD ELASTIC RUBBER/KEVLAR/COTTON
	CORD SHOCK RUBBER/KEVLAR/COTTON
MIL-C-5651T3	CORD ELASTIC EXERCISER
MIL-C-572	CORD NOMEX 2400 DENIER
	WIRE ELEC TEFLON TFE
	YARN POLYESTER 1100 DENIER
MIL-C-572TP	THREAD NOMEX
MIL-C-675	COATING HFA ANTIGLAR OPTICAL
MIL-C-7219T1C1	FABRIC DUCK NYLON NATURAL
MIL-C-7350T2	FABRIC NYLON
MIL-C-7438	CORE HONEYCOMB/ALUMINUM FACE PLATES
	ADHESIVE BONDED
MIL-C-7515	CORD NYLON CORELESS
	LACING TAPE NOMEX 950HOT16
MIL-C-7515T1	WEBBING NYLON 400 LB
MIL-C-8021	NYLON ORANGE
MIL-C-8061	FABRIC NYLON MESH 8885
MIL-C-81393A	FABRIC NOMEX SIMPLEX
MIL-C-81773	COATING 03-W-40 POLYURETHANE GLOSS WHITE
	COATING 7312-A01F GRAY POLYURETHANE
MIL-C-8193	GASKET MATERIAL RUBBER SILICONE/NOMEX
MIL-C-81986	LAMIN EPOXY/GLASS WITH HRH
MIL-C-83286	COATING 0[illegible]-BK-29 POLYURETHANE FLAT BLACK
	COATING 03-BL-51 POLYURETHANE FLAT BLUE
	COATING 03-GY-62 POLYURETHANE FLAT LIGHT
	GRAY
	COATING 03-W-40 POLYURETHANE GLOSS WHITE
	COATING 17875 POLYURETHANE WHITE
	COATING 33798 TOPCOAT WITH POLYAMIDE
	PRIMER
	COATING 463-7-26/A276/X-369
	COATING 821-331 POLYURETHANE FLAT WHITE
	COATING 821-331 POLYURETHANE FLAT WHITE
	WITH PRIMER
	COATING 821-400 POLYURETHANE GLOSS WHITE
	COATING 821-425/515-700 PRIMER
	COATING 822-327 POLYURETHANE FLAT LT GRAY
	COATING 823-363 POLYURETHANE GLOSS ORANGE
	COATING 824-408 POLYURETHANE GLOSS ORANGE

MSFC-HDBK-527 REV F ■ 9999942 0006663 T ■

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
MIL-C-83286	COATING 828-310 POLYURETHANE FLAT BLACK
	COATING A276/02-Y-24
	COATING A276/P527D
	COATING POLYURETHANE BLACK
	COATING POLYURETHANE LT GRAY 36622
	COATING POLYURETHANE ORANGE INTL 12197
	COATING POLYURETHANE WHITE
	COATING POLYURETHANE YELLOW 23785
	COATING POLYURETHANE YELLOW 33538
	COATING POLYURETHANE YELLOW/SUPER KOROPON
	COATING TOPCOAT YELLOW
	COATING YELLOW 33798 PRIMER/EPOXY TOPCOAT
	CONFIG NYLON VELCRO/COTTON
	CONFIG NYLON VELCRO/COTTON COF
	LAMIN DUCT 02GY3 TC URETHANE 17875
MIL-C-83286:PAINT	COATING PAINT YELLOW 33798 URETHANE/PRIMER EPOXY AMIDE
MIL-C-83286B	COATING 03-BK-28 WITH CATALYST
	COATING 643-18-1 WHITE
MIL-C-83286T1	COATING 823-311 POLYURETHANE FLUOREL/ YELLOW
	COATING POLYURETHANE TOPCOAT #1
MIL-C-83286T3	COATING 513-703/821-331/910-736
MIL-C-83429T2C1	GLOVE CLOTH NOMEX RTV 157 GREEN
MIL-C-83723	CONNECTOR ELECTRICAL
	CONNECTOR SEALING PLUG AL/NI
MIL-C-8603	CLAMP NEOPRENE/AL MS21919DG
MIL-C-9084	LAMIN EPOXY/GLASS E720
MIL-C-9084 T2 C3	FABRIC GLASS/SILICONE
MIL-C-9084 T4&7	FABRIC GLASS/SILICONE
MIL-C-9084C2	LAMIN EPOXY/GLASS
MIL-C-9084CT8A	LAMIN EPOXY/GLASS
MIL-C-9084T8	FABRIC RTV E 1581 GLASS
MIL-C39029/4	CONNECTOR NB-CR-20
MIL-C39029/5	CONNECTOR NB-CS-16
	CONNECTOR NB-CS-20
MIL-D-13796	ADHESIVE DAP
MIL-D-23377DT1	COATING 33798 TOPCOAT WITH POLYAMIDE PRIMER
MIL-D-3464T2	BAG NYLON MESH X-1591
MIL-D-3716T4GRH	DESICCANT SILICA GELL
MIL-D-5516CB	RUBBER NITRILE N304-75
MIL-E-480	COATING ENAMEL BLACK
MIL-F-1148	FIBRE VULCANIZED GRADE CH
MIL-F-14072	COATING GREY ENAMEL/PRIMER
	FINISH SYSTEM P213B
MIL-F-14256	FLUX
MIL-F-14THFH	MOLD COMPOUND DUREZ 11844 BLK
MIL-F-19207B	FUSE HOLDER
MIL-F-20329	FLUX SOLDER
MIL-F-218040ET1C2	FASTENER VELCRO ARAMID HOOK 65 AND LOOP
MIL-F-21840	FASTENER SCOTCHMATE SJ3571 LOOP PS ADHESIVE
	FASTENER SCOTCHMATE SJ3572 HOOK PS ADHESIVE

SPECIFICATION	DESIGNATION
MIL-F-21840	FASTENER VECRO HI-AIR NYLON HOOK 65 WITH NOMEX GROUND
	FASTENER VELCRO MID-TEMP NYLON HOOK AND LOOP
	FASTENER VELCRO NYLON HOOK AND LOOP
	FASTENER VELCRO NYLON HOOK AND LOOP WITH FR127A ADHESIVE
	FASTENER VELCRO NYLON LOOP WITH FR127 ADHESIVE
	MULTI-LAYERED INSULATION TEDLAR/MYLAR/ VELCRO #65
	WEBBING NYLON/VELCRO/NOMEX/METALIZED UTILITY STRAP
MIL-F-21840C1	FASTENER VELCRO NYLON HOOK 80 BACKING 0199W
	FASTENER VELCRO NYLON LOOP 100 BACKING 0199
	FASTENER VELCRO NYLON LOOP 1000
	FASTENER VELCRO NYLON LOOP 1000 PS 0100
	FASTENER VELCRO NYLON LOOP 1000 WITH PS 0104 ADHESIVE
MIL-F-21840C2	FASTENER VELCRO ALL NON MELTING ARAMID LOOP 2000
MIL-F-21840C4	FASTENER VELCRO NOMEX HI-AIR LOOP 2000 BACKING 0199W
MIL-F-21840ET1C2	FASTENER VELCRO NYLON HOOK AND LOOP 65 BACKING 0399
MIL-F-21840T1C1	FASTENER VELCRO NOMEX LOOP 1000 BACKING 039
	FASTENER VELCRO NYLON HOOK 65
	FASTENER VELCRO NYLON HOOK 65 WITH PS 0104 ADHESIVE
MIL-F-21840T1C2	FASTENER APLIX 820 NOMEX NON-MELTING HOOK
	FASTENER APLIX 820 NOMEX NON-MELTING HOOK AND LOOP
	FASTENER APLIX 820 NOMEX NON-MELTING LOOP
	FASTENER VELCRO NYLON HAQ 12-2-100 LOOP
	FASTENER VELCRO NYLON HOOK 66 NON MELTING ARAMID GROUND
MIL-F-21840T2C1	FASTENER VELCRO LOOP NYLON 80 WITH PS 0172
	FASTENER VELCRO NYLON HOOK 80 WITH PS 0172
	FASTENER VELCRO NYLON HOOK AND LOOP 80 BACKING PS 0172
MIL-F-21840T2C2	WEBBING NMX/HOOK HAQ-12-1-100
MIL-F-21840T2C3	FASTENER APLIX 810 POLYESTER HOOK
	FASTENER APLIX 810 POLYESTER LOOP
MIL-F-21F40	MULTI-LAYERED INSULATION TEDLAR/MYLAR/ 3M838/VELCRO
MIL-F-47018CC	FABRIC PHENOLIC/SILICA
MIL-F-47254	INSULATION FOAM POLYURETHANE OPEN CELL
MIL-F-495	COATING CONVERSION BL OXIDE INORGANIC
MIL-F-4995	FLUX SOLDER
MIL-F-66651/1	LAMIN STYRENE/GLASS REXOLITE 2200
MIL-F-81254	INSULATION FOAM URETHANE
MIL-F-8791	TEFLON TFE VIRGIN

SPECIFICATION	DESIGNATION
MIL-F-8799	TAPE SCOTCHCAL 3650
MIL-G-18586C2	RUBBER NITRILE
MIL-G-21164	GREASE AEROSHELL 17
MIL-G-22050	RUBBER EPR E688-70
MIL-G-23827	LUBE GREASE AEROSHELL XSG6249
	LUBE GREASE BRAYCOTE 6275
MIL-G-25013C	LUBE GREASE SUPERMIL ASU31052
MIL-G-276170T4	LUBE GREASE BRAYCOTE 600
MIL-G-27617C	LUBE GREASE FOMBLIN Z-LHT
	LUBE GREASE TRIBOLUBE 10
MIL-G-27617CT1	LUBE GREASE BRAYCOTE 804
	LUBE GREASE BRAYCOTE 804A
MIL-G-27617CT2	LUBE GREASE BRAYCOTE 805A
MIL-G-27617CT3	LUBE GREASE AIRCRAFT
	LUBE GREASE BRAYCOTE 806
	LUBE GREASE BRAYCOTE 806A
	LUBE GREASE TRIBOLUBE 10C
MIL-G-27617D	LUBE GREASE TRIBOLUBE 15
MIL-G-27617DT3	LUBE GREASE TRIBOLUBE 16
MIL-G-27617T1	LUBE GREASE D840924A T1
MIL-G-27617T3	LUBE GREASE TRIBOLUBE 10C
MIL-G-3036	RUBBER NEOPRENE
	RUBBER SYNTHETIC MS35489
MIL-G-4343	LUBE DRY MOLYKOTE 55M
MIL-G-47219	LUBE GREASE HALOCARBON 25-5S
MIL-G-53636	LAMIN EPOXY/GLASS/DC3140 COATED
MIL-G-55636	LAMIN EPOXY/GLASS
	LAMIN EPOXY/GLASS B10-108-63
MIL-G-81188B	GLOVE GS/FRP-2
MIL-G-81322	GREASE HYDROCARBON
MIL-G-81322B	GREASE MOBIL 28
	LUBE SYNTON PAO 100
MIL-G-9954	BEADS GLASS SODALIME TY SILICA
MIL-H-27267	HOSE LINER PTFE
MIL-H-45444	CORD JET HMX AND RL-20-X
MIL-H-62217-1	HOSE SILICONE PUROSIL 70-087
	HOSE SILICONE PUROSIL 80-100
MIL-H-83282A	TUBING POLYOLEFIN DUAL WALL HST
MIL-H-83282FBG	LAMIN COTTON/PHENOLIC
MIL-I-10A	BERYLLIA (BEO 99.5%) INORGANIC
MIL-I-15126	TAPE P214 GLASS/ACRYLIC
	TAPE PAPER BACKED
	TAPE SCOTCH 54 POLYESTER PS
MIL-I-15126F	TAPE SCOTCH 5 POLYESTER
MIL-I-15126MFT	TAPE P252 MYLAR PS
MIL-I-15126TGFT	TAPE ELECTRIC POLYESTER TYPE GFT PS ADHESIVE
	TAPE SCOTCH 27 GLASS/RUBBER/ADHESIVE
MIL-I-16923	POTTING COMPOUND SCOTCHCAST 247
	ROD CP2-4289
MIL-I-1693	POTTING COMPOUND STYCAST 1090/C9
MIL-I-17205	FABRIC GLASS FIBER VARNISHED
MIL-I-17384TG	COATING LACQUER PAINT QUICK DRY
MIL-I-18057	TUBING HYGRADE SR398 HA1
MIL-I-18057HA-1	TUBING FIBERGLASS/SILICONE

SPECIFICATION	DESIGNATION
MIL-I-18746	FABRIC FIBERGLASS 2103/108 TFE
MIL-I-19166	TAPE FLUORGLAS 2915 PS ADHESIVE
	TAPE MYSTIK 7000 GLASS/SILICONE ADHESIVE
	TAPE MYSTIK 7001 GLASS/SILICONE ADHESIVE
	TAPE P212 GLASS/SILICONE ADHESIVE
	TAPE SCOTCH 69 GLASS/SILICONE/ADHESIVE
MIL-I-22129	TUBING PTFE NON-HEAT SHRINK
MIL-I-2212G	TUBING HEAT SHRINKABLE
MIL-I-22444	TAPE ADHESIVE SILICONE GLASS/REINFORCED
	TAPE SILICONE MOX/FIBERGLASS
MIL-I-22444ATSB	TAPE STRETCH SILICONE RUBBER
MIL-I-23053	TUBING KORVEX FEP HS
MIL-I-23053/1	TUBING NEOPRENE RT510 HST
	TUBING NT120 NEOPRENE HST
MIL-I-23053/1-1	TUBING POLYCHLOROPRENE HST
MIL-I-23053/11	TUBING KORVEX FEP HS
	TUBING TEFLON FEP HST
MIL-I-23053/12	TUBING ELEC PTFE HST DUAL WALL
	TUBING KORVEX FEP HS
	TUBING KORVEX TFE HS
	TUBING PTFE HST
	TUBING TEFLON TFE HST
MIL-I-23053/13	TUBING FLUOROELASTOMER HS
MIL-I-23053/4	TUBING POLYOLEFIN DUAL WALL HST
MIL-I-23053/4C1	TUBING POLYOLEFIN HST THERMAPOD
	TUBING POLYOLEFIN RET125 HST
MIL-I-23053/4C2	TUBING POLYOLEFIN RTA125 HST
MIL-I-23053/4C3	TUBING POLYOLEFIN DWP125
MIL-I-23053/5	TUBING FP301 INSULTITE HST
	TUBING FP301 TYPE 2 POLYOLEFIN HS
	TUBING POLYOLEFIN RNF100
	TUBING POLYOLEFIN RT876 HST
	TUBING SUMITUBE POLYOLEFIN HST
MIL-I-23053/5 C2	TUBING POLYOLEFIN GPO135 T2
MIL-I-23053/5C1	TUBING POLYOLEFIN GPO135 BLK
	TUBING POLYOLEFIN RNF100
MIL-I-23053/5C2	TUBING FP301 TYPE 2 POLYOLEFIN HS
MIL-I-23053/5C3	TUBING INSULTITE VFP876 HST BLACK
MIL-I-23053/6	TUBING POLYOLEFIN GPR135 BLK
	TUBING POLYOLEFIN RT360 TYPE 2
MIL-I-23053/8	TUBING INSULTITE KYNAR HST CLEAR NOC
	TUBING KYNAR PVF175 HS
	TUBING KYNAR RT850 HST
MIL-I-23594	TAPE SCOTCH 61 TFE/SILICONE PS
MIL-I-23594A	TAPE MYSTIK 7503 TFE/SILICONE ADHESIVE
MIL-I-23594AT1	TAPE TEFLON/SILICONE
MIL-I-23594T1	TAPE P421 TEFLON SILICONE ADHESIVE
MIL-I-23594T2	TAPE SCOTCH 62 TFE/SILICONE PS ADHESIVE
MIL-I-2394 T1	TAPE P423 TFE/SILICONE
MIL-I-24092	VARNISH PHENOLIC ELECTRIC INSULATION
MIL-I-24092C200	VARNISH SILICONE DC997
MIL-I-24204	FABRIC NOMEX 410
	PAPER 414 NOMEX
	PAPER NOMEX TYPE 410/ARAMID
MIL-I-3190	TUBING FIBERGLASS/SILICONE 3298-1

MSFC-HDBK-527 REV F ■ 9999942 0006665 3 ■

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
MIL-I-3190	TUBING HYGRADE SR398 HB1
	TUBING RAYON
MIL-I-3190 CL B	SLEEVING PVC POLYMER P/N 96M87264-1
MIL-I-3190TD	TUBING HYGRADE SR398 HB1
MIL-I-43435	LACING TAPE GUDE-SPACE 18DPT-H
MIL-I-43553	ADHESIVE ARMSTRONG C1 EPOXY
	INK CAT-L-INK 50-100R/20
	INK CAT-L-INK 50-70 EPOXY
	INK CAT-L-INK 50-700/1
	INK CAT-L-INK 50-700R/20
MIL-I-43553 INK	CONFIG PWB/COATED WITH PR1568
MIL-I-45208	TEFLON TFE VIRGIN
MIL-I-45208A	YARN TFE TYPE 302
MIL-I-46010	LUBE SANDSTROM 9A
MIL-I-46058	COATING 683-3-3Y POLYURETHANE
	COATING DC Q3-6500 SILICONE
	COATING PC 29/29M POLYURETHANE
	COATING URALANE 5750 A/B
MIL-I-46058C	COATING CONFORMAL CONATHANE CE1155 POLYURETHANE
	COATING URALANE 5750 A/B
MIL-I-46058ER	COATING PC12-007 EPOXY
MIL-I-46058TYER	LAMIN EPOXY/PC12-007M COATED
MIL-I-46058TYUR	COATING POLYURETHANE PR1568 CONFORMAL
MIL-I-46058XY	COATING PYRALENE C
MIL-I-631	FILM MYLAR POLYESTER
MIL-I-631TA	FILM MYLAR POLYESTER
MIL-I-631TGFF	TAPE 925 ALUMINUM WITH POLYESTER ADHESIVE
MIL-I-6869	IMPREGNANT BRAZING
MIL-I-6903	INK MARKING PARACHUTES
MIL-I-695	INSULATION PAPER ARMITE SLOT
MIL-I-695TR	INSULATION ELECTRICAL RAG PAPER
	PAPER COPACO
MIL-I-81550	POTTING COMPOUND SYLGARD 182
MIL-I-81765/1	POLYOLEFIN HS COMPONENTS
MIL-I-81765/T	TUBING ECC POLYOLEFIN HS
MIL-L-15719	LUBE DRY MOLYKOTE 44
MIL-L-20213	LITHIUM HYDROXIDE INORGANIC
MIL-L-2105	LUBE OIL QUAKER STATE 90
MIL-L-23398	LUBE DRY LUBRIBOND 220 FILM
	LUBE DRY LUBRIBOND A
MIL-L-233983	LUBE FILM SOLID
MIL-L-25567C	LEAK DETECTOR SHERLOCK 5 SEC
MIL-L-3150	LUBE OIL PRESERVATIVE
MIL-L-46010	LUBE DRY DRILUBE 6A
	LUBE DRY KALGARD RA MOS2
	LUBE DRY TIOLUBE 460 MS21063
MIL-L-46147	LUBE DRY MOLYKOTE 3402 MOS2
MIL-L-51131	LITHIUM-STEARATE
MIL-L-60326	LUBE FLUOROCARB MS136 TELOMER
	LUBE TFE FLUOROCARBON TELOMER
MIL-L-60326T1	MOLD RELEASE AGENT TFE MS-122
MIL-L-6085	LUBE GREASE BRAYCO 885B
MIL-L-6805	COATING LACQUER 604-37038
MIL-L-7808	LUBE OIL SYNTHETIC BASE

SPECIFICATION	DESIGNATION
MIL-L-81329	LUBE DRY FILM
MIL-L-81352	LACQUER ACRYLIC
MIL-L-83429T1	FABRIC AROMATIC POLYAMIDE
MIL-L-8937	LUBE DRY NPI14
	LUBE DRY TIOLUBE 460 MS21063
	LUBE EVERLUBE 620A
MIL-M-14	MOLD COMPOUND DAP FS6 CAF BLUE
	MOLD COMPOUND DAP SDG 7717
	MOLD COMPOUND POLYESTER/GLASS MAI-60
	MOLD COMPOUND RX 3-1-530
	TERMINAL STRIP 221 PHENOLIC
MIL-M-146	MOLD COMPOUND DAP DC-62
MIL-M-14CFI-10	POTTING COMPOUND FM1132 PHENOLIC
MIL-M-14F	MOLD COMPOUND DAP FS5 BLACK 8000
	MOLD COMPOUND DAP FS80/GLASS FILLED
	MOLD COMPOUND FIBERITE FM-8130
	MOLD COMPOUND FIBERITE FM4030-190
	MOLD COMPOUND PLENCO 1528
	POTTING COMPOUND E9405 EPOXY/GLASS
MIL-M-14FMFH	MOLD COMPOUND DUREZ 11864 PHENOLIC
MIL-M-14FMMI-5	MOLD COMPOUND M2840 MELAMINE
MIL-M-14FSDG	MOLD COMPOUND FS10 DAP
MIL-M-20693	NYLON 6/6
MIL-M-24325GEI	MOLD COMPOUND EPOXY/GLASS FILLED
MIL-M-27274	RUBBER SILICONE DC8-2318U
MIL-M-38510	CERAMIC MICROCIRCUIT/INORGANIC
MIL-M-38527/8A-001-P	SEALANT SIL-PAD K10 INSULATOR KAPTON XT POLYIMIDE FILM WITH BORON NITRIDE FILLED SILICONE RUBBER
	SEALANT SIL-PAD K4 INSULATOR RUBBER WITH KAPTON XT FILM
MIL-M-43719T1C1	TAPE SCOTCHCAL 3650
	TAPE SCOTCHCAL 3651 RED
MIL-M-81594T3	TUBING KYNAR RT850 HST
MIL-M-81594T4	INK K486 HOT STAMP BLUE-BLACK
MIL-M-83436	CONFIG PWB/COATED WITH PR1568
MIL-MMM-A-132	ADHESIVE EPOXY PATCH KIT 9340
MIL-N-25027	LUBE DRY
MIL-P-13305	ACRYLIC TRANSPARENT
MIL-P-13949	COATING CONFORMAL CONATHANE CE1155 POLYURETHANE
	CU CLAD FR4/PCB WITH MS-470 COATING
	LAMIN EPOXY/GLASS FIBER
	LAMIN EPOXY/GLASS FR TYPE GF
	LAMIN EPOXY/GLASS/DC3140 COATED
	LAMIN EPOXY/GLASS/URALANE 5750 COATED
	LAMIN EPOXY/GLASS/URALANE 5753 COATED
	LAMIN MICAPLY EG818T
	LAMIN OVERCOAT WITH 1B31/FC721
	LAMIN URALANE 5570 COATED WITH FC721
MIL-P-13949/10/13	LAMIN POLYIMIDE/GLASS
MIL-P-13949/13	PRINTED WIRING BOARD COPPER CLAD/POLYIMIDE GLASS/CAT-L-INK 50-100 MARKING 1 TO 3 MIL S THICK/URALANE 5075 CONFORMAL COATING 3 TO 5 MILS THICK

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
MIL-P-13949/3	LAMIN EPOXY/GLASS GENERAL PURPOSE
MIL-P-13949/4	LAMIN EPOXY/GLASS
MIL-P-13949E	LAMIN EPOXY/GLASS TAYLORCLAD FIREBAN
	LAMIN EPOXY/GLASS VIBRATION DAMPER
MIL-P-13949F	COATING 2A53 EPOXY ON MULTIWIRE CIRCUIT BOARD
MIL-P-13949GA	LAMIN TEFLON TFE/GLASS
MIL-P-13949GEN	LAMIN EPOXY/GLASS
MIL-P-13949GFN	LAMIN EPOXY/GLASS
MIL-P-13949GI	LAMIN POLYIMIDE/GLASS
MIL-P-13949TYGF	LAMIN EPOXY/GLASS WITH EPOXYLITE 9653
MIL-P-15024	LABEL METALPHOTO
MIL-P-15035C	LAMIN PHENOLIC/COTTON TYPE FBM
MIL-P-15035FBE	LAMIN COTTON/PHENOLIC
MIL-P-15037TGME	LAMIN MELAMINE/GLASS G9-818
MIL-P-15047NPG	LAMIN PHENOLIC/NYLON
MIL-P-15328	COATING WASH PRETREATMENT
MIL-P-15328C	COATING PRIMER P605-66/C152-66 BLUE
MIL-P-157	PAPER ONION SKIN
MIL-P-16232TM	COATING PHOSPHATE (INORGANIC)
MIL-P-17091	NYLON PLASTIC
MIL-P-18177	LAMIN EPOXY/GLASS
	LAMIN EPOXY/GLASS FF91
	LAMIN EPOXY/GLASS FR4
	LAMIN EPOXY/GLASS WITH HRH
MIL-P-18177C	LAMIN EPOXY/GLASS
MIL-P-18177GEB	LAMIN EPOXY/GLASS
MIL-P-18177GEBG11	LAMIN EPOXY/GLASS
MIL-P-18177GEE	LAMIN EPOXY/GLASS COATED WITH CE1155
	LAMIN EPOXY/GLASS L-P-509 TYPE G10
	LAMIN EPOXY/GLASS N4105
MIL-P-18484	RUBBER NITRILE
MIL-P-19468A	TEFLON TFE VIRGIN
MIL-P-19833	MOLD COMPOUND DAP DC-62
MIL-P-19834T1	LABEL IDENTIFICATION ALUMINUM FOIL/PS ADHESIVE 467
MIL-P-19834T2	TAPE SCOTCH 583 ACRYLIC ADHESIVE
MIL-P-20444	COATING PRECUSSION
MIL-P-2224	TEFLON TFE VIRGIN
MIL-P-22241	CLAMP SLEEVE TEFLON TFE
	TEFLON TFE VIRGIN
MIL-P-22241B	TEFLON G-83 TFE
MIL-P-22241T1	TEFLON TFE VIRGIN
MIL-P-23377	COATING 463-7-26/A276/X-369
	COATING 513-703/821-331/910-736
	COATING 513X332/910X457 PRIMER
	COATING 515-703/910-736 PRIMER
	COATING 821-331 POLYURETHANE FLAT WHITE WITH PRIMER
	COATING A1716/BT1-1
	COATING A276/02-Y-24
	COATING A276/P527D
	COATING CHEMGLAZE Z306
	COATING EPOXY POLAMIDE WITH POLYURETHANE OVERCOAT

SPECIFICATION	DESIGNATION
MIL-P-23377	COATING EPOXY/POLYAMIDE
	COATING POLYAMIDE EPOXY
	COATING POLYAMIDE EPOXY PRIMER YELLOW
	COATING POLYAMIDE WITH CHEMGLAZE Z306
	COATING POLYIMIDE EPOXY YELLOW TC
	COATING TOPCOAT YELLOW
MIL-P-23377:PRIMER	COATING PAINT YELLOW 33798 URETHANE/PRIMER EPOXY AMIDE
MIL-P-23377C	COATING POLYAMIDE EPOXY
MIL-P-23377C1	COATING EPOXY/POLYAMIDE CONVERT
	COATING POLYAMIDE EPOXY
MIL-P-23377D	COATING EPOXY/POLYAMIDE
	COATING POLYAMIDE EPOXY
MIL-P-23377DT2	COATING EPOXY/POLYIMIDE
MIL-P-24074	FLUOROGOLD TFE/GLASS 25%
MIL-P-24074T1GB	FLUOROGOLD TFE/GLASS 25%
MIL-P-25421BT2	LAMIN EPOXY/GLASS
MIL-P-25690A	ACRYLIC SHEET SI60948 STRETCH
	ACRYLIC TYPE 350S
MIL-P-25732	RUBBER NITRILE
	RUBBER NITRILE N304-75
	RUBBER NITRILE/TFE TEFLON
MIL-P-26514A	INSULATION FOAM POLYURETHANE 3-4LBS
MIL-P-26514E	INSULATION FOAM TENNECO 6LBN BLACK
MIL-P-26514T1	INSULATION FOAM POLYURETHANE FLEXIBLE
MIL-P-38477	INK SCREEN DAYGLO SUPER 67
	INK SUPER 67 SIGNAL GREEN
	LABEL IDENTIFICATION MYLAR ADHESIVE 850 CLEAR
	LABEL IDENTIFICATION MYLAR ADHESIVE 850/ RED
	LABEL IDENTIFICATION MYLAR ADHESIVE 850/ SILVER
	LABEL IDENTIFICATION MYLAR ADHESIVE 853/ CLEAR
MIL-P-387	EXPLOSIVE PETN
MIL-P-40619C2GA	INSULATION FOAM POLYSTYRENE LOW DENSITY FR
MIL-P-46036	KEL-F 81
	KEL-F CTFE UNPLASTICIZED
MIL-P-46036T1	KEL-F 81
	KEL-F CTFE UNPLASTICIZED
MIL-P-46036T2	KEL-F 81
MIL-P-46112	FILM KAPTON H
MIL-P-46120	MOLD COMPOUND POLYSULFONE P-1720
MIL-P-46129	MOLD COMPOUND POLYPHENYLENE OXIDE
MIL-P-46174C40GE	CONNECTOR PLASTIC WTB56SAD11SY-17
MIL-P-5315	RUBBER NITRILE N602-7
MIL-P-5315B	RUBBER NITRILE
MIL-P-5425	PLASTIC PLEXIGLASS 2 UVA
MIL-P-55028G3	KEL-F 81
MIL-P-5510	RUBBER NITRILE (NRB)
MIL-P-5516	RUBBER NITRILE 1070W VIX
	RUBBER NITRILE CPD 7377
MIL-P-5516CB	RUBBER NITRILE
MIL-P-55617TLGF	LAMIN EPOXY/GLASS TYPE GF

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006667 7

SPECIFICATION	DESIGNATION
MIL-P-55640	LAMIN URALANE 5570 COATED WITH FC721
MIL-P-8116	PUTTY ZINC CHROMATE GENERAL PURPOSE
	SEALANT ZINC CHROMATE GRAY
MIL-P-8184	PLASTIC PLEXIGLASS 55
MIL-P-83461	RUBBER NITRILE N766-75
MIL-P-85582T1	COATING EPOXY PRIMER 37051
	COATING PRIMER/CHEMGLAZE A276
	COATING WATER BASE PRIMER
MIL-P-8585	COATING ZINC CHROMATE
MIL-P-997GSG	LAMIN SILICONE/GLASS
MIL-R-25897	RUBBER VITON FLUID RESISTANT
MIL-R-25897TIG70	RUBBER VITON 840627 (1320-75)
MIL-R-25988	FABRIC NOMEX 2002/FLUOROSILICONE
	RUBBER FLUOROSILICONE
	RUBBER FLUOROSILICONE L677-70
	RUBBER FLUOROSILICONE LS53
MIL-R-25988/1	RUBBER FLUOROSILICONE L449-65
MIL-R-25988B	RUBBER VULCON CL 1 GR 40 T2
MIL-R-25988C1	RUBBER FLUOROSILICONE L449-65
	RUBBER FLUOROSILICONE L677-70
	RUBBER FLUOROSILICONE L806-80
MIL-R-25988T1C1	RUBBER FLUOROSILICONE L737-65
MIL-R-25988T2C1	RUBBER FLUOROSILICONE
MIL-R-3065	CLAMP SILICONE/GLASS
	RUBBER NEOPRENE E
	RUBBER NEOPRENE ZX2002
	RUBBER SILICONE SE4404
MIL-R-3065 TV'S	RUBBER NITRILE
MIL-R-3065S/SC	RUBBER NEOPRENE
MIL-R-3065SC515	COATING NEOPRENE LN2500A
MIL-R-3065TA612	CLAMP SILICONE/GLASS
MIL-R-398TACC	RDX
MIL-R-46082T1	ADHESIVE LOCTITE 601 EPOXY
	ADHESIVE LOCTITE 75
MIL-R-46846	TUBING POLYOLEFIN RT876 HST
MIL-R-46846T1C1	TUBING NEOPRENE RT510 HST
MIL-R-46846T2	TUBING NT120 NEOPRENE HST
MIL-R-46846T5	TUBING INSULTITE VFP876 HST BLACK
	TUBING POLYOLEFIN GPO135 BLK
MIL-R-46846T5C1	TUBING POLYOLEFIN RT876 HST
MIL-R-47252	COATING RESIN EPOXY
MIL-R-5315	SEALANT RUBBER 27980
MIL-R-5847	RUBBER SILICONE 4216A
MIL-R-5847C13	RUBBER SILICONE RTV 4515
MIL-R-5847C2A	RUBBER SILICONE DURO 40
MIL-R-5847C2G50	GASKET SILICONE/MONEL
MIL-R-6130T1GRA	RUBBER SPONGE NEOPRENE
	SPONGE RUBBER NEOPRENE
MIL-R-6855C1/2	RUBBER NITRILE
MIL-R-6855C2G4	RUBBER NITRILE
MIL-R-6855C2TBG80	RUBBER NEOPRENE
MIL-R-6855G30	RUBBER NITRILE GRADE 30
MIL-R-6855G40	RUBBER NITRILE GRADE 40
MIL-R-6855G50	RUBBER NITRILE GRADE 50
MIL-R-6855G60	RUBBER NITRILE GRADE 60

SPECIFICATION	DESIGNATION
MIL-R-6855G70	RUBBER NITRILE GRADE 70
MIL-R-6855G80	RUBBER NITRILE GRADE 80
MIL-R-7362	RUBBER NITRILE MS29561-005
MIL-R-83248	RUBBER FLUOREL V23
	RUBBER FLUOROCARBON
	RUBBER VITON 744-75
	RUBBER VITON A
	RUBBER VITON A V23
	RUBBER VITON A V709-90
	RUBBER VITON FLUID RESISTANT
	RUBBER VITON V709-90
	RUBBER VITON V747-75
	SEALANT VITON AP2709
MIL-R-83248A	RUBBER VITON SR2702-72
MIL-R-83248C1	RUBBER FLUOREL FC2174
	RUBBER FLUOROELASTOMER O-RING
MIL-R-83248C1T1	RUBBER VITON V747-75
MIL-R-83248C2	FABRIC KEVLAR 1813-2 WITH VITON
MIL-R-83248T1	RUBBER VITON 9009-90
MIL-R-83248T1C	RUBBER VITON O-RING S/A 2-012
	RUBBER VITON O-RING S/A 2-016
	RUBBER VITON O-RING S/A 2-024
MIL-R-83248T1C1	RUBBER SR2702-75
	RUBBER VITON 9009-75
	RUBBER VITON E60C
	RUBBER VITON FLUID RESISTANT
	RUBBER VITON NE8477
	RUBBER VITON O-RING S/A 2-012
	RUBBER VITON O-RING S/A 2-014
	RUBBER VITON O-RING S/A 2-016
	RUBBER VITON O-RING S/A 2-020
	RUBBER VITON O-RING S/A 2-035
	RUBBER VITON O-RING S/A 2-343
	RUBBER VITON V747-75
	SEALANT FLUOROCARBON M83248/2-916
	SEALANT FLUOROCARBON MS83248/2-904
MIL-R-83248T1C2	RUBBER FLUOREL V23
	RUBBER VITON 9009-90
	RUBBER VITON FLUID RESISTANT
	RUBBER VITON V709-90
	SEALANT FLUOROCARBON M83248/2-916
	SEALANT FLUOROCARBON MS83248/2-904
MIL-R-83248T1CT	RUBBER VITON V747-75
MIL-R-83248T2C1	COMPOSITE VITON E60C/NOMEX HT426
	RUBBER VITON E60C/HT426 NOMEX
	RUBBER VITON FLUID RESISTANT
	RUBBER VITON MDAC 18210-16
MIL-R-83248T2C2	RUBBER VITON FLUID RESISTANT
	RUBBER VITON V709-90
MIL-R-83286	RUBBER VITON FLUID RESISTANT
MIL-R-832T1C1	RUBBER VITON FLUID RESISTANT
MIL-R-8791	RUBBER NITRILE/TFE TEFLON
MIL-R-9299	LAMIN EPOXY/PHENOLIC
MIL-R-9300	ADHESIVE EPON 815 EPOXY
	ADHESIVE EPON 828 EPOXY

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
MIL-R-9300	LAMIN EPOXY/GLASS E720
	LAMIN FIBERITE 1
MIL-R83248/1904	RUBBER VITON V747-75
MIL-S-0024041	POTTING COMPOUND PROSEAL 799
MIL-S-13865T1	FABRIC GLASS/LAMIN 3171/PT401
MIL-S-17917	LAMIN BALSA WOOD/ALUMINUM FACING
MIL-S-22473	ADHESIVE LOCTITE HV
MIL-S-22473D	ADHESIVE LOCTITE A
MIL-S-22499	LAMIN SHIM/POLYESTER ADHESIVE
MIL-S-22499C2T1	SHIM AL 50524H39
MIL-S-23190D	CABLE TIES TY-27M NYLON
	CABLE TIES TY-28M NYLON
MIL-S-23586	FELT TECKFELT 45-09811
	RUBBER SILICONE RTV 634
MIL-S-25948	SUNGLASSES AND CASE
MIL-S-4383	RUBBER BUNA N
MIL-S-46163	SEALANT THREAD LOCKING
MIL-S-46163 T2 GR W	SEALANT THREAD LOCKING COMPOUND
MIL-S-81087	LUBE OIL VERSILUBE F50 SILICONE
MIL-S-8516ET2C3	SEALANT PROSEAL 727-2-3 POLYSULFIDE
MIL-S-8660	RUBBER SILICONE THERMAL CONDUCTIVE
MIL-S-8660B	LUBE GREASE DC4 SILICONE
MIL-S-8802	SEALANT POLYSULFIDE PR1422
	SEALANT POLYSULFIDE PROSEAL 890
MIL-S-8802CA	ADHESIVE POLYSULFIDE PR14600
MIL-STD-104B	TUBING POLYOLEFIN B322 HST
MIL-STD-105	COATING 2A53 EPOXY ON MULTIWIRE CIRCUIT BOARD
MIL-STD-1247B	TAPE MARKING 02
MIL-STD-417SB	RUBBER NITRILE
MIL-T-19166	TAPE P211 GLASS/SILICONE ADHESIVE
MIL-T-23053/5C2	TUBING FP301 TYPE 2 POLYOLEFIN HS
MIL-T-23594	TAPE TEFLON
MIL-T-24204	TUBING NOMEX/TEFLON/SILICONE
MIL-T-25421T1C2	TUBING G10 130C FIBERGLASS/EPOXY
MIL-T-277	TAPE TEFLON PTFE ANTISEIZE
MIL-T-27730A	TAPE TEFLON
	TAPE TEFLON PTFE ANTISEIZE
	TAPE TEFLON THREAD
	TAPE THREAD SEAL PTFE AQM
MIL-T-4053	TAPE GLASS/THERMOSET PS
MIL-T-43435	LACING TAPE 217
	LACING TAPE AIR-TEX 17
	LACING TAPE HT-20 LOC A NOMEX
	LACING TAPE POLYESTER
	LACING TAPE POLYESTER/DACRON
MIL-T-43435B	LACING TAPE AROMATIC POLYAMIDE
	TAPE BUNDLING GLASS FABRIC
MIL-T-43435BT1	LACING TAPE NYLON
MIL-T-43435BT4	LACING TAPE GLASS/TFE
MIL-T-43435CT3	LACING TAPE TFE/RUBBER H 231H
MIL-T-43435T1	LACING TAPE BRAID NYLON
	LACING TAPE GUDE-LACE
	LACING TAPE NYLON/DACRON LC136
MIL-T-43435T1/C	LACING TAPE NYLON/RUBBER 18H
MIL-T-43435T2E	LACING TAPE POLYESTER AIR-TEX 217
MIL-T-43435T3	LACING TAPE TFE 2560
MIL-T-43435T5	LACING TAPE NOMEX/P/N 950H0T16
MIL-T-43636	CABLE TIES NOMEX/POLYETHYLENE FC4101
	CONFIG NYLON VELCRO/COTTON
	CONFIG NYLON VELCRO/COTTON COF
	MULTI-LAYERED INSULATION AL/KAPTON/DACRON/NOMEX/MYLAR
	THREAD NOMEX
MIL-T-43636/1E	FABRIC NOMEX 7878 G650
	YARN NOMEX R79-430
MIL-T-43636T1	INSULATION BLANKET KAPTON/DACRON/NOMEX
	MULTI-LAYERED INSULATION GOLDIZED KAPTON/DACRON MESH/NOMEX
MIL-T-43636T12E	WEBBING NYLON/VELCRO/NOMEX/METALIZED
	UTILITY STRAP
MIL-T-43636T2E	FABRIC COTTON S55 F/P/VELCRO/NOMEX
MIL-T-4363C	CURTAIN HYGIENE CLOSURE
MIL-T-50036	POWDER TALC
MIL-T-5038	CABLE TIES NOMEX/POLYETHYLENE FC4101
	TAPE NYLON WEBBING WHITE
	WEBBING NOMEX TAPE
	WEBBING NYLON 1000 LB
	WEBBING NYLON TAPE
MIL-T-5038 MOD	WEBBING NOMEX 9476 FIREPROOFED
MIL-T-5038T3	FABRIC NOMEX 9476
	TAPE NOMEX 9476
	WEBBING NOMEX TAPE
MIL-T-50884	ADHESIVE JW7-12 ACRYLIC
MIL-T-5544	LUBE CPD GRAPHITE/PETROLATUM
	LUBE MOS2 PETROLATUM
MIL-T-5608 CET4	NYLON 6/6
MIL-T-5608T4	WEBBING NOMEX 9960 FR
MIL-T-5608TSCLC	WEBBING NYLON 300 LB
MIL-T-5661	TAPE COTTON ALL TYPES
MIL-T-60394A	TAPE SCOTCHMOUNT 4032
MIL-T-713	LACING TAPE NYLON
MIL-T-713TN	LACING TAPE NATURAL FIBER/WAX
MIL-T-7928	TERMINAL LUG
MIL-T-81088T2C2	THREAD NOMEX E77701/450 ROYAL BLUE SIZE 3/64
MIL-T-81533	ADHESIVE PRESSURE SENSITIVE
MIL-T-81772AT1	COATING YELLOW 33798 PRIMER/EPOXY TOPCOAT
MIL-T-83483	LUBE GREASE PETROLATUM/MOS2
	LUBE MOS2 PETROLATUM
MIL-T-8363	WEBBING NYLON
MIL-T-87128	MULTI-LAYERED INSULATION AL/MYLAR/KEVLAR/DACRON
	MULTI-LAYERED INSULATION FEP/GLASS/POLYIMIDE/KEVLAR
	MULTI-LAYERED INSULATION RADIATION SHIELD TEFLON
	THREAD ARAMID
	THREAD KEVLAR SIZE E
MIL-T-87130T1C2	WEBBING KEVLAR 550 LB

MSFC-HDBK-527 REV F ■ 9999942 0006669 0 ■

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
MIL-T-87130T6C4	WEBBING KEVLAR 1000 LB
MIL-T-87130T6C9	WEBBING KEVLAR 6000 LB
MIL-T-9906	TAPE MYLAR/ACRYLIC PS ADHESIVE
MIL-T-9906A	TAPE MYLAR/ACRYLIC PS ADHESIVE
MIL-V-1137GCB	COATING ISONEL 31 POLYESTER
MIL-V-1137TMGCB	COATING VARNISH 961
MIL-V-173	VARNISH SYNTHITE AC29-76
MIL-W-16878-E	WIRE ELEC TEFLON TFE
MIL-W-16878/1	WIRE ELEC PVC
MIL-W-16878/10	WIRE ELEC POLYETHYLENE
MIL-W-16878/11	WIRE ELEC FEP
MIL-W-16878/13	WIRE ELEC FEP
MIL-W-16878/17	WIRE ELEC PVC INSULATED POLYAMIDE JACKET
MIL-W-16878/25	WIRE ELEC TEFLON TFE
MIL-W-16878/25BFE9	WIRE ELEC TEFLON TFE
MIL-W-16878/4 T S.W.	WIRE CABLE SHIELDED
MIL-W-22579/3	WIRE ELEC PTFE/GLASS FEP
MIL-W-22759	CABLE TIES TEFZEL TY-RAP TYZ
	WIRE ELEC ETFE TEFZEL
	WIRE ELEC ETFE WHT 20 AWG
	WIRE ELEC TEFLON TFE
MIL-W-22759 1-18-9	WIRE ELEC PTFE/GLASS FEP
MIL-W-22759 18-20-9	WIRE ELEC RAYCHEM 44 MYLAR/KAPTON
	WIRE ELEC WITH METAL BRAID SHIELD
MIL-W-22759 32-20-9	WIRE ELEC RAYCHEM 44 MYLAR/KAPTON
MIL-W-22759/1	WIRE ELEC PTFE/GLASS FEP
MIL-W-22759/12	INSULATION WIRE CU/TFE/GL
MIL-W-22759/17	WIRE ELEC ETFE TEFZEL
MIL-W-22759/18	WIRE ELEC ETFE TEFZEL
MIL-W-22759/35	WIRE ELEC ETFE TEFZEL
MIL-W-22759/4	WIRE ELEC PTFE/GLASS FEP
	WIRE ELEC TEFLON TFE
MIL-W-22759/5	WIRE ELEC TFE MINERAL FILLED
MIL-W-22759/6	WIRE ELEC TFE MINERAL FILLED
MIL-W-22759/7	WIRE ELEC TFE MINERAL FILLED
MIL-W-22759/8	WIRE ELEC TFE MINERAL FILLED
MIL-W-25038	WIRE ELEC TEFLON TFE
MIL-W-27265	WEBBING NYLON WOVEN
MIL-W-27500-24	WIRE ELEC 2-WIRE CABLE
MIL-W-27500/20	WIRE ELEC MD 913 FLUOROCARBON POLYIMIDE INSULATION
MIL-W-27657	WEBBING NYLON WOVEN
MIL-W-27657T5	WEBBING NYLON 9000 LB
MIL-W-38283 T1	DUCT SILICONE/HT6 NOMEX
MIL-W-38283T1	WEBBING NOMEX
MIL-W-38283T15	WEBBING NOMEX 22.4OZ
MIL-W-38283T2	WEBBING NOMEX
	WEBBING NOMEX 14.4OZ
	WEBBING NYLON
	WEBBING NYLON/VELCRO/NOMEX/METALIZED
	UTILITY STRAP
	WEBBING STRAP NYLON FIRE/WATERPROOF
	WEBBING STRAP NYLON/FC4101
MIL-W-38283T4	WEBBING NMX/HOOK HAQ-12-1-100
MIL-W-40880	WEBBING 3600 COND. R

SPECIFICATION	DESIGNATION
MIL-W-4088T1A	WEBBING NYLON FIRE/WATER PROOF
MIL-W-4088T2	WEBBING NOMEX 9981 FIREPROOFED
	WEBBING NOMEX/COATING FC4101-C-16
MIL-W-4088T24	WEBBING NYLON 5000 LB
MIL-W-4088T6	WEBBING NYLON 2500 LB
MIL-W-5625	WEBBING NYLON 2300 LB
	WEBBING TEXTILE/NYLON/TUBULAR
MIL-W-56256	WEBBING DACRON
MIL-W-5664	WEBBING TEXTILE ELASTIC COTTON
MIL-W-583	WIRE MAGNET RECTANGULAR POLYVINYL FORMAL COATED CLASS 105 TYPE 2 AND 4
MIL-W-583C	WIRE ELEC MAGNET CL200 TYPE K POLYESTER
MIL-W-583M	WIRE ELEC MAGNET CL 220
MIL-W-6712C	WIRE ZINC METALLIZING
MIL-W-7866	LUBE DRY MOLYKOTE Z MOS2 INORGANIC
MIL-W-81044	TAPE SCOTCH 1267 AL/ACRYLIC/ADHESIVE
	WIRE ELEC RAYCHEM 44 ALL GAGES
MIL-W-81044/12	INSULATION WIRE POLYOLEFIN/KYNAR
	WIRE ELEC PD-219-21
	WIRE ELEC RAYCHEM 44 ALL GAGES
MIL-W-81116B	TAPE LOOP-TAPE NOMEX
MIL-W-81381	WIRE ELEC FEP WITH POLYIMIDE TAPE
	WIRE ELEC FEP/POLYIMIDE TAPE
	WIRE ELEC TEFLON TFE
MIL-W-81381/11	WIRE ELEC FEP WITH POLYIMIDE TAPE
MIL-W-81381/11-8	WIRE ELEC WITH POLYIMIDE INSULATION
MIL-W-81381/17	WIRE ELEC FEP/POLYIMIDE TAPE
MIL-W-81381/17-20-X	WIRE ELEC WITH POLYIMIDE INSULATION
MIL-W-81381/17-22-0	INSULATION BLACK FROM STRANDED ELECTRICAL WIRE
MIL-W-81381/17-22-X	WIRE ELEC WITH POLYIMIDE INSULATION
MIL-W-81822/13	WIRE ELEC ETFE TEFZEL
MIL-W-81822/3	ADHESIVE ABLEFILM 550 EPOXY
	WIRE ELEC KYNAR PVF
MIL-W-83420	CABLE CRES LUBRICATED
MIL-Y-1140	FABRIC FIBERGLASS STYLE 7628
	TUBING FIBERGLASS S1600-H
	TUBING FIBERGLASS SLV 1200
MIL-Y-1140H	FABRIC FIBERGLASS/SILICONE 03080
MIS-13865 T1	COATING PT401 RESIN
MLO311-0010	MULTI-LAYERED INSULATION KAPTON/BETA
MM5DS-V156-78	TAPE MYLAR/SILVER ADHESIVE
MMC P/N 55LC	COATING 856-204/855-225/850-204
MMC STP 70021	ADHESIVE EPON 828/DTA 7500 GLASS
MMC-EPS-30027	COATING EPOXY POLYAMIDE ON STAINLESS STEEL
MMC-STP-30151	COATING CHEMGLAZE Z306/9924
MMC-STP-30170	COATING EPOXY POLAMIDE WITH POLYURETHANE OVERCOAT
	COATING POLYAMIDE WITH CHEMGLAZE Z306
MMC/STM K792	COATING INORGANIC WHITE
MMC/STM K794	COATING CHEMGLAZE Z306
MMCJ536B	TAPE SCOTCH 346 DOUBLE COAT PS
MMM-A-121	ADHESIVE STABOND T161
MMM-A-132	ADHESIVE EA901/B1
	ADHESIVE FILM FM1000 POLYAMIDE

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
MMM-A-132	ADHESIVE FILM FM300 EPOXY
MMM-A-132T1/2	ADHESIVE FILM FM123-2LVC EPOXY
MMM-A-132T2	LAMIN FIBERITE T50/934 GRAPHITE WITH ADHESIVE FILM HT424 AND PRIMER
MMM-A-134T1	ADHESIVE EPOXY ER825A
MMMS F 411 A050	LACING TAPE A050
MMS 1282004	TUBING TEFLON TFE HST
MMS 1282016	TUBING TEFLON TFE HST
MMS 1282020	TUBING TEFLON TFE HST
MMS 1282040	TUBING TEFLON TFE HST
MMS 1282205	TUBING TEFLON TFE HST
MMS 1282212	TUBING TEFLON TFE HST
MMS 1282216	TUBING TEFLON TFE HST
MMS 1282218	TUBING TEFLON TFE HST
MMS 1282220	TUBING TEFLON TFE HST
MMS 144	TUBING TEFLON TFE HST
MMS 1440003	TUBING TEFLON TFE HST
MMS 1440004	TUBING TEFLON TFE HST
MMS 1440005	TUBING TEFLON TFE HST
MMS 1440007	TUBING TEFLON TFE HST
MMS 1440008	TUBING TEFLON TFE HST
MMS 1440009	TUBING TEFLON TFE HST
MMS 1440010	TUBING TEFLON TFE HST
MMS 1440012	TUBING TEFLON TFE HST
MMS 1440014	TUBING TEFLON TFE HST
MMS 1440016	TUBING TEFLON TFE HST
MMS 1440018	TUBING TEFLON TFE HST
MMS 1440020	TUBING TEFLON TFE HST
MMS 1440022	TUBING TEFLON TFE HST
MMS 1440024	TUBING TEFLON TFE HST
MMS 144006	TUBING TEFLON TFE HST
MMS 1440078	TUBING TEFLON TFE HST
MMS 1440125	TUBING TEFLON TFE HST
MMS 1440250	TUBING TEFLON TFE HST
MMS 1440500	TUBING TEFLON TFE HST
MMS 1440750	TUBING TEFLON TFE HST
MMS 1441000	TUBING TEFLON TFE HST
MMS 1441250	TUBING TEFLON TFE HST
MMS 145 045	TUBING FEP 100 HST
MMS 145 060	TUBING FEP 100 HST
MMS 145 092	TUBING FEP 100 HST
MMS 145 1.3	TUBING FEP 100 HST
MMS 145 115	TUBING FEP 100 HST
MMS 145 180	TUBING FEP 100 HST
MMS 145 197	TUBING FEP 100 HST
MMS 145 225	TUBING FEP 100 HST
MMS 145 290	TUBING FEP 100 HST
MMS 145-031	TUBING FEP 100 HST
MMS 145-365	TUBING FEP 100 HST
MMS 1450031	TUBING TEFLON FEP HST
MMS 1450045	TUBING TEFLON FEP HST
MMS 1450092	TUBING TEFLON FEP HST
MMS 1450141	TUBING TEFLON FEP HST
MMS 1450158	TUBING TEFLON FEP HST
MMS 1450180	TUBING TEFLON FEP HST

SPECIFICATION	DESIGNATION
MMS 1450225	TUBING TEFLON FEP HST
MMS 1450290	TUBING TEFLON FEP HST
MMS 145036	TUBING TEFLON FEP HST
MMS 1450365	TUBING TEFLON FEP HST
MMS 1450440	TUBING FEP 100 HST
MMS 1450500	TUBING TEFLON FEP HST
MMS 1450666	TUBING TEFLON FEP HST
MMS 203	TUBING FIBERGLASS
	TUBING FIBERGLASS S1600-H
	TUBING FIBERGLASS SLV 1200
MMS 250	TUBING PTFE NON-HEAT SHRINK
MMS 2500750	TUBING PTFE NON-HEAT SHRINK
MMS 250250	TUBING PTFE NON-HEAT SHRINK
MMS 250313	TUBING PTFE NON-HEAT SHRINK
MMS 250375	TUBING PTFE NON-HEAT SHRINK
MMS A569	MULTI-LAYERED INSULATION AL/KAPTON/DACRON/NOMEX/MYLAR
MMS Y985	MULTI-LAYERED INSULATION AL/KAPTON/DACRON/NOMEX/MYLAR
MMS-C-132A	RUBBER SILICONE ON AL/SILASTIC E
MMS-E-300	CABLE ELEC TFE/BEN-HAR GLUE
	CABLE ELEC TFE/BEN-HAR SLEEVE
	CABLE ELEC TFE/VARGLAS SLEEVE
	WIRE ELEC TEFLON TFE
MMS-E-300-2002	WIRE ELEC TEFLON TFE
MMS-E-300-2003	WIRE ELEC TEFLON TFE
MMS-E-300-2202	WIRE ELEC TEFLON TFE
MMS-E-3002002	CABLE ELEC TFE/BEN-HAR GLUE
MMS-E-3002202	WIRE ELEC TEFLON TFE
MMS-E-646	WIRE ELEC TFE/GLASS WARP
MMS-E-654 1010	WIRE ELEC TEFLON TFE
MMS-E-658 1002	WIRE ELEC TEFLON TFE
MMS-E-658 1009	WIRE ELEC TEFLON TFE
MMS-E-658 1010	CABLE ELEC RTM437 CU IMBEDDED IN FEP WITH TEFLON OVERWRAP
MMS-E-6581002	WIRE ELEC TEFLON TFE
MMS-E-6581010	WIRE ELEC FEP
MMS-E-659	WIRE ELEC FEP/POLYIMIDE TAPE
MMS-E-737	WIRE ELEC
MMS-E-741	WIRE ELEC FEP/POLYIMIDE TAPE
	WIRE ELEC WRAPPED IN P2650 SILICONE TAPE
MMS-F-144	TUBING PLASTIC
	TUBING PTFE HST
	TUBING PTFE SHRINKABLE
MMS-F-1440078	TUBING PTFE HST
	TUBING PTFE SHRINKABLE
MMS-F-203	TUBING FIBERGLASS SLV 1200
MMS-F-416	LACING TAPE PTFE ENAMELED
MMS-F-4160125	LACING TAPE PTFE ENAMELED
MMS-F-416C125	LACING TAPE F416 TEFLON COATED
	LACING TAPE PTFE ENAMELED
MMS-F-417	LACING TAPE PTFE/GLASS
	TAPE PLASTIC
MMS-F118	TUBING FP301 INSULTITE HST
MMS-J-517	TAPE P2650 SILICONE RUBBER NON ADHESIVE

MSFC-HDBK-527 REV F 9999942 0006671 9

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
MMS-J-690	MULTI-LAYERED INSULATION AL/KAPTON/DACRON/ NOMEX/MYLAR
MMS-J-690A	TAPE 925 ALUMINUM WITH POLYESTER ADHESIVE
MMS-K010	INK MARKING A423-66 BASE T252-66 CONVERTER
MMS-N-425	LUBE GREASE KRYTOX 240AC
MMS-N308A	LUBE DRY DRILUBE 842
MMS-Y-824	COMPOUND LEAK TEST
MMS-Y-824C100	COMPOUND LEAK TEST N727C
MMS-Y-846	DEVELOPER D90
	PENETRANT I-319
MMS-Y-933A000	FILM ACLAR 933A
MMS2518	ADHESIVE POLYFREEZE P146 EPOXY
MMS2 8432129	WIRE ELEC TEFLON TFE
MMS26462202	WIRE ELEC TFE/GLASS WARP
MM 1100 TY16C	WIRE ELEC MAGNET CL 220
MP871-0077-0001	WIRE ELEC FEP/POLYIMIDE TAPE
MP871-0077-0003	WIRE ELEC FEP/POLYIMIDE TAPE
MP871-0077-0004	WIRE ELEC FEP/POLYIMIDE TAPE
MP871-0077-0006	WIRE ELEC FEP/POLYIMIDE TAPE
MP871-0077-0009	WIRE ELEC FEP/POLYIMIDE TAPE
MP871-0077-0010	WIRE ELEC FEP/POLYIMIDE TAPE
MP871-0084-0014	WIRE ELEC FEP/POLYIMIDE TAPE
MP871-0086-0002	WIRE ELEC FEP/POLYIMIDE TAPE
MP871-0086-0003	WIRE ELEC FEP/POLYIMIDE TAPE
MP871-0087-0003	WIRE ELEC FEP/POLYIMIDE TAPE
MP872-0279-002	WIRE ELEC TEFLON TFE
MP872-0310-0002	WIRE ELEC FEP/POLYIMIDE TAPE
MPP-105M330M01	FABRIC NOMEX FDC 307 F/WP
MPS MPQ 121	LUBE DRY VITROLUBE 1220
MPS-MA-0105-330	FABRIC NOMEX FDC 307 F/WP
MPS-MPQ-121A	LUBE DRY VITROLUBE 1220
MR 5004-112	PLASTIC LEXAN MARGARD MR5004-112
MR-21081	LUBE FLUOROLUBE GRADE FS5
MR3244-PO713074	KEL-F CTFE UNPLASTICIZED
MS20813	LAQUER YELLOW
MS21122	TEFLON TFE RED STRIPED
MS21919WCJ7	CLAMP CUSHION FLOUROSILICONE
MS27472-73	CONNECTOR ELECTRICAL 18-32 #4
	CONNECTOR ELECTRICAL 18-32P #1
MS27473E12F985	CONNECTOR ELECTRICAL
MS27473E24F35P	CONNECTOR ELECTRICAL 73E
MS27473E24F35S	CONNECTOR ELECTRICAL 73E
MS27488-16	CONNECTOR NB-GSP-16
MS27488-20	CONNECTOR NB-GSP-20
MS27497E24F35P	CONNECTOR ELECTRICAL 97E
MS27497E24F35S	CONNECTOR ELECTRICAL 97E
MS27506F10-2	CONNECTOR ELECTRICAL
MS27511C10C	RUBBER SILICONE NOC ZZ-R-765
MS27738-21A	MICRO-SWITCH 12TL1-1A
MS27980	WEBBING NYLON/VELCRO/NOMEX/METALIZED UTILITY STRAP
MS28775	RUBBER NITRILE N304-75
MS3368-1	LACING TAPE NYLON
MS3450L36-10SW	CONNECTOR ELECT SILICONE RUBBER/CERAMIC
MS3450L36-1D	CONNECTOR ELECT SILICONE RUBBER/CERAMIC

SPECIFICATION	DESIGNATION
MS3459L20-15P	CONNECTOR ELECTRICAL PLUG
MS3475L12-10P	CONNECTOR ELECTRICAL
MS83248/1-904	RUBBER VITON 9009-75
MS83248/1-916	RUBBER FLUOROCARBON
MS83248/2-904	RUBBER FLUOROCARBON
MS9068-014	RUBBER SILICONE O-RINGS
MSFC 276-11XXXX	TUBING POLYOLEFIN HS FLAME RESISTANT
MSFC 276-23XXXX	TUBING THERMOFIT 218 HST CONVLEX
MSFC 276-32XXXX	TUBING POLYVINYLCHLORIDE (PVC)
MSFC 384	COMPOUND LEAK TEST MMSY824C100
MSFC 40M39569	CONNECTOR ELECTRICAL
MSFC 418	INSULATION FOAM ECCOFOAM TYPE SH
MSFC SPEC 276	WIRE ELEC POLYIMIDE/KYNAR RT850
MSFC SPEC 671	COATING TOPCOAT YELLOW
MSFC STD-383	INK 40M12864 BLACK
MSW-309	FABRIC POLYBENZIMIDAZOLE (PBI)
MT3-13-1	FILLER CORFIL 615 EPOXY
MX4926	FABRIC CARBON PHENOLIC ABLATIVE
NAI-1328B	SEALANT EPOXY CORROSION INHIBITOR 71-Y-1
NAS-9-15246	FABRIC NETTING/POLYPROPYLENE
	RUBBER 10006149
	RUBBER NEOPRENE
	RUBBER NEOTEX ELASTIC
	RUBBER SILICONE 1235-70
	SHIELD POLYCARBONATE PLASTIC
NAS1089-24	STREAMER WARNING COTTON
NASD-QTS-1023	LAMIN EPOXY/GLASS PC BOARD
NASDA-QTS-1023	LAMIN EPOXY/GLASS CIRCUIT BOARD
	LAMIN EPOXY/GLASS PC BOARD
NASDA-QTS-24308/101	CONNECTOR D-SUB ND101-9S-C/ND101-9P-C
NAT 666014	RUBBER EPR AS014
NAV ORD WS17360	PROPELLANT
NCFI-25-13	INSULATION FOAM NCFI 6A POLYISOCYANURATE
	INSULATION FOAM NCFI 7A POLYISOCYANURATE
NE-1-M-12	WIRE ELEC POLYIMIDE INSULATION
NFPA 701	FABRIC SUNBRELLA FIRESIST 8601 ARTIC BLUE
NLS6E16-XX	SINGLE LAYER TAPE/BENDIX CLAMP
	TAPE VITON-FLUOREL/CLAMP
NLSOT20-35S	CONNECTOR INSERT SILICONE/RUBBER
NPI-14	LUBE DRY NPI14
NS-101	RUBBER NEOPRENE
NS-105BB	RUBBER NEOPRENE
NSN 8040-00-142-9193	ADHESIVE CYANOACRYLATE
OSM 241-2	CONNECTOR 2001-5119-00
P.O. 98365	KEL-F 81
P/N 001-130-0102	FASTENER VELCRO NYLON LOOP WITH PS 0102 ADHESIVE
P/N 10-250	RUBBER SILICONE CL 3A GR 25
P/N 10-256	RUBBER SILICONE CL 3B GR 30
P/N 100-001-012-0172AB	FASTENER VELCRO NYLON 100 BACKING 0172AB
P/N 100-004-233-3099AB	FASTENER VELCRO HOOK AND LOOP 100 BACKING 3099AB
P/N 100-080-012-0100AB	FASTENER VELCRO NYLON HOOK ADHESIVE BACK
P/N 100-082-233-3099AB	FASTENER VELCRO HOOK AND LOOP 100 BACKING 3099AB

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006672 0

SPECIFICATION	DESIGNATION
P/N 1000-001-0107AA	FASTENER VELCRO NYLON LOOP 1000 BACKING PS 0107
P/N 1000-001-012-8299RA	FASTENER VELCRO NYLON LOOP 1000 FR 8299
P/N 1000-001-330-8299RA	FASTENER VELCRO NYLON LOOP 1000 FR 8299
P/N 1000-003-117-0199W	FASTENER VELCRO NOMEX HI-AIR LOOP 2000 BACKING 0199W
P/N 1000-004-233-3099	FASTENER VELCRO HOOK AND LOOP 1000 BACKING 0399
P/N 1000-082-233-3099	FASTENER VELCRO HOOK AND LOOP 1000 BACKING 0399
P/N 10753-0001	INSULATION MSA-1
P/N 194260	FASTENER VELCRO NOMEX LOOP 2000 WITH PS 0372 ADHESIVE
P/N 2-014-5604-70	RUBBER SILICONE O-RINGS
P/N 200-001-012-0199W	FASTENER VELCRO NYLON LOOP 100 BACKING 0199
P/N 2000-001-012-0100AB	FASTENER VELCRO LOOP 2000 BACKING 0100AB
P/N 2000-001-750-0172AB	FASTENER VELCRO NYLON LOOP 2000 BACKING 0172
P/N 2000-1000-330-0172	FASTENER VELCRO NYLON LOOP 2000 BACKING 0172
P/N 2032	CABLE HIGH VOLTAGE RUBBER SILICONE INSULATED WITH VITON SLEEVING
P/N 2495-SW10082	PWB COPPER CLAD GLASS FABRIC EPOXY RESIN FR4 COATED WITH HUMISEAL/INDICATOR MODEL 2495 ATTACHED TO BOARD
P/N 38100-01	LAMIN THORNEL P75 2K/ERLX 1962 UNIDIRECTIONAL POLYMERIC RESIN/CARBON
P/N 3977-01	ADHESIVE 3977-01 THERMAL EPOXY
P/N 40-9570100050	RUBBER SILICONE CV1144-0
P/N 4701-05-201-25-1537	INSULATION FOAM URETHANE PORON CELLULAR FR
P/N 5772-50	ADHESIVE AVIMID N COMPOSITE
P/N 6753067-29	SLEEVING EXPANDO 686 TIGHTWEAVE POLYPHENYLENE SULFIDE
P/N 8600750	TUBING VITON HST
P/N 9005960-1	COATING POLYURETHANE PR1535
P/N 9006116	INK MARKING UVEXS 105E BLACK
P/N 960-C-1778	RUBBER SILICONE CL 2A & 2B GR 60
P/N 980-N-702	RUBBER SILICONE CL 1A & 1B GR 80
P/N 990015-0002	RUBBER SANTOPRENE
P/N CVA6R2D-15Z16	CONNECTOR ELECTRICAL
P/N LS40554-001	LABEL IDENTIFICATION FLEXOFILM CHROME MYLAR WITH NAZDAR MY111 BLACK INK WITH ACRYLIC PS V23 ADHESIVE
P/N LS40554-003	LABEL IDENTIFICATION FLEXOFILM CHROME MYLAR WITH NAZDAR MY111 BLACK INK WITH ACRYLIC PS V23 ADHESIVE
P/N LS40572-001	LABEL IDENTIFICATION FLEXOFILM CHROME MYLAR WITH NAZDAR MY111 BLACK INK WITH ACRYLIC PS V23 ADHESIVE
P/N LS40572-003	LABEL IDENTIFICATION FLEXOFILM CHROME MYLAR WITH NAZDAR MY111 BLACK INK WITH ACRYLIC PS V23 ADHESIVE
P/N LS41533-001	LABEL IDENTIFICATION FLEXOFILM ACRYLIC PS ADHESIVE V23 WITH NAZDAR MY111 BLACK AND MY124 ORANGE INK
P/N LS41533-002	LABEL IDENTIFICATION FLEXOFILM ACRYLIC PS ADHESIVE V23 WITH NAZDAR MY111 BLACK AND MY124 ORANGE INK
P/N LS41567-001	LABEL CAUTION FLEXCON MYLAR WITH ACRYLIC PS ADHESIVE V23 WITH NAZDAR MY111 BLACK AND PANTONE 803C FLUORESCENT YELLOW INK
P/N TYZ527M	CABLE TIES TEFZEL TY-RAP TYZ
PD-219-21	WIRE ELEC RAYCHEM 44 ALL GAGES
PD-42	LUBE DRY TIOLUBE 460 MS21063
PD-4700187-060	TEFLON PTFE DISCS
PD-6400520	INSULATION FOAM ABLESTICK/ECCOSPHERES S1
PDL 500-2.5	INSULATION FOAM PDL61
	INSULATION FOAM PDL62
PILE 29200	SOCKS PATAGONIA
PMIC-SPEC-4223	MULTI-LAYERED INSULATION TEDLAR/ALUMINIZED MYLAR
PMIC-SPEC-4224	MULTI-LAYERED INSULATION TEDLAR/ALUMINIZED MYLAR
PO R23948	RUBBER KALREZ 4079 COMPOUND
PPP-C-1752	INSULATION FOAM POLYETHYLENE FLEXIBLE
PPP-C-1752 T1C2	INSULATION FOAM UNICELLULAR POLYETHYLENE
PPP-C-1752T1C2	INSULATION FOAM POLYETHYLENE FLEXIBLE
PPP-T-60 T4C1	TAPE VINYL/COTTON SP252
	TAPE VINYL/COTTON TUCK 91B
PPP-T-66	TAPE SCOTCH 474
PPP-T-66E T2	TAPE PACKAGING VINYL WHITE
PR MIL-P-23377D	COATING YELLOW 33798 PRIMER/EPOXY TOPCOAT
PR9-181-1	ADHESIVE EPON 815 EPOXY
PS 14030 COMP 2	ADHESIVE EA828/DTA/AL POWDER EPOXY
PS 14032 TY1	ADHESIVE EA828/VERSAMID 125/FILLED
PS 14106	LAMIN KEVLAR 49/LY8061 EPOXY
Q3-6527 A/B	RUBBER SILASTIC E RTV SILICONE
QQ-N-281B	GASKET SILICONE/MONEL
QQ-S-571WS	SOLDER KESTER SN 96
RA 3265-02	LAMIN EPOXY/GLASS PC BOARD
RA 4747-00	LAMIN EPOXY/GLASS PC BOARD
RAU-ADT-16A.2.1-4033[2P440-874008]	CONNECTOR CIRCUIT BOARD FR4 DOUBLE WIDTH FLIGHT WITH HUMISEL 1B31 ACRYLIC TYPE AR CONFORMAL COATING
RB 3835-01	LAMIN EPOXY/GLASS PC BOARD
RB0130-087	INSULATION FOAM POLYURETHANE
RB0130-089	POLY (AMIDE-IMIDE)
RB0140-017 TY1	LUBE DRY EVERLUBE 811
RB0120-005 T8	RUBBER SILICONE RTV 77
RB0130-013E T2/CYL#86-1 TO 12	TUBING LAMINATED/ROLLED PTFE RESIN/GLASS FABRIC BASE
RB0130-013E T2/CYL#86-14 TO 18	TUBING LAMINATED/ROLLED PTFE RESIN/GLASS FABRIC BASE
RB0130-019	PAPER FIBERFRAX

MSFC-HDBK-527 REV F 9999942 0006673 2

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
RB0130-040 T2	RUBBER SILICONE NOC
RB0130-091 T1	RUBBER SILICONE NOC
RB0130-091 T2	RUBBER SILICONE NOC
RB0130-093 T1C1	RUBBER VITON FLUID RESISTANT
RB0130-094 CE	KEL-F CTFE UNPLASTICIZED
RB0130-097 CF	TEFLON TFE VIRGIN
RB0130-100 CB	TUBING TEFLON FEP HST
RB0130-101 CL C	TUBING TEFLON FEP HST
RB0140-007 RE	LUBE DRY INLOX 88
RB0150-042	LACING TAPE AROMATIC POLYAMIDE
RC1108 4334-113	COATING GRAY TOPCOAT/KOROPON PRIMER
RCA 1986843	COATING EPOXY POLYAMIDE GRAY
RD-004-056A	RUBBER SILICONE RTV R2500
	RUBBER SILICONE RTV R2501
RD-2974	HOSE LINER TEFLON CONDUCTIVE
REDUC UGLZ-1498	INK UNIGLAZE UGLZ8000 BLACK
REVAC DG 2010	REVAC DD2010
RF 307435-92	TAPE SCOTCH 92 SILICONE/POLYMIDE BACKING
RF 3884-00	LAMIN EPOXY/GLASS PC BOARD
RF-443	FABRIC KELVAR 29
RG 3161U	CABLE COAXIAL TFE/FEP
RP-6401-A	POTTING COMPOUND REN RP6401A POLYURETHANE BLUE
RP-6402-A	POTTING COMPOUND REN RP6402A POLYURETHANE RED
RS-128585-SS-3	SEALANT BARCO THERMOSET
RS-99450-SS-3	SEALANT BARCO THERMOSET
RT	ADHESIVE EA934NA EPOXY
RT-1800	MARKER SLEEVING HT-TMS KYNAR/VITON HS
RTK06-8-7P	CONNECTOR ELECTRIC
RTM 437 E 658	CABLE ELEC RTM437 CU IMBEDDED IN FEP WITH TEFLON OVERWRAP
SAE 100R3	HOSE PARFLEX 540N/POLYURETHANE
SAE 100R7	HOSE HYTRON PRESSURE
	HOSE PARFLEX 558H/POLYESTER
SE-C-0093	TAPE LACING S199 POLYIMIDE
SE-T-0082	MULTI-LAYERED INSULATION DACRON NET B4A/ POLYBENZIMIDAZOLE/TG15000 SILICONE GLASS/ TAPE G411970 ALUMINUM/KAPTON ADHESIVE
SE-T-0092	FABRIC PBI
	MULTI-LAYERED INSULATION DACRON NET B4A/ ALUMINUZED KAPTON/PBI/ALUMINIZED KAPTON RIPSTOP
	MULTI-LAYERED INSULATION DACRON NET B4A/ KAPTON/ALUMINUM/PBI
	THREAD PBI FRL-S152
SE0622	PROPELLANT BSM U7P19048
SE0729	PROPELLANT LINER BSM U7L004B
SE0733	RUBBER BUNA N
SE5549U	P-GASKET BMS 1-59 SILICONE
SEC329U-BWU	WIRE ELEC URETHANE 29 AWG
SED33101584-302	FILM PHOTO PAN 2415
SED33101586-302	FILM PHOTO PAN 2415
SED33102094-301	RUBBER BAND NATURAL OR SYNTHETIC SIZE 64
SED38106631	HOSE FLEX TEFLON/1% CARBON

SPECIFICATION	DESIGNATION
SED48101653-501	SOAP NON-FOAMING
SF-142B	CABLE ELECTRICAL 07145 AG COATED CU WITH TEFLON AND ALUMINIZED MYLAR
SF-88T-0	PAPER E-20
SF-96-5	RUBBER SILICONE RTV 630/50% OIL
SK83-02968	RUBBER POLYURETHANE RUCOTHANE AX5225 WITH COTTON FLOC
SK83-0296B	RUBBER POLYURETHANE RUCOTHANE AX5225 WITH COTTON FLOC
SK85052-3	FABRIC SILICONE/GLASS
SL-20	FLASHLIGHT STREAMLITE 20
SL-20-16C	WIRE ELEC KAPTON/FEP SPECIAL
SM3500-41	RUBBER SILICONE T8296
SP-AI-0040	THREAD CRES 300 SERIES
SP-R-0022A	COATING CHEMGLAZE A276/02-GN-40 PRIMER
	COATING CHEMGLAZE II A276/9922 PRIMER
	COATING CHEMGLAZE Z302/02-GN-40PRIMER
	COATING CHEMGLAZE Z302/9922 PRIMER
	COATING CHEMGLAZE Z302/9924 PRIMER
	COATING CHEMGLAZE Z306/9922 PRIMER
	COATING CHEMGLAZE Z306/9924
	FILM LH94-5 CLEAR
	FILM POLYURETHANE/CARBON LH86-13
	INK MARKING 44
	LUBE GREASE RHEOLUBE 738
SPARMAT 03:37	FASTENER VELCRO HOOK 80 LOOP 2000
SS-24-301	WIRE ELEC PVC
SS-323242T5C8	WEBBING KEVLAR 1000 LB
ST0120-LB0001	ADHESIVE PLASTILOCK 729-3/728
ST0130LB0007	LAMIN EPOXY/BORON/TITANIUM SHEET
ST0140GB0002T2	LUBE DRY EVERLUBE 811
ST0140GB002T1	LUBE DRY MOS2/SILICATE
ST0370-001	MULTI-LAYERED INSULATION AL/AU COATED/ VELCRO/ACRYLIC
ST0370-002	MULTI-LAYERED INSULATION AL/AU COATED/ VELCRO/ACRYLIC
ST0370-003	MULTI-LAYERED INSULATION PLASTIC/VELCRO/AU COATED
ST0370-004	MULTI-LAYERED INSULATION PLASTIC/VELCRO/AU COATED
ST10F071-02	FELT TFE
ST10F1369-01	SLIPPER SOCKS
ST10L069-01	LEATHER DEERSKIN
ST10L719-01	EMBLEM CLOTH NASA
ST10P1165-01	EMBLEM CLOTH SHUTTLE
ST10P804	TISSUE TOILET SINGLEFOLD
ST10P827-01	PAPER KLEENEX TISSUE PACK
ST10U1879	FABRIC COTTON/POLYESTER
ST10U1879-01	FABRIC COTTON/POLYESTER
ST116041-01	FABRIC ORTHO 116
ST11A8 0-01	FABRIC NOMEX WITH ZEPEL/ARMALON URETHANE COATED NY
ST11A830-01	FABRIC NOMEX WITH ZEPEL/ARMALON
	FABRIC NOMEX/ARMALON BACKING
	FABRIC NOMEX/ARMALON/URETHANE COATED NY

MSFC-HDBK-527 REV F 9999942 0006674 4

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
ST11B823	BLANKET SURVIVAL SPACE BRAND
ST11C1325	FABRIC COTTON CHEESE CLOTH
ST11C709	FABRIC COTTON 100%(FR/2%THPOH)
ST11C709-01	FABRIC 100% COTTON FR 7 OZ BLUE
	FABRIC COTTON FLAME RETARDANT
	FABRIC FR COTTON 7 OZ/SQ YD
ST11C709-02	FABRIC COTTON 100%(FR/2%THPOH)
	FABRIC COTTON 7 OZ/LINING 4 OZ FR
	FABRIC FR COTTON 7 OZ/SQ YD
ST11C709-03	FABRIC 100% COTTON FR 7 OZ BLUE
ST11C802	SOCKS COTTON TUBE
ST11C802-01	SOCKS TUBE 90% COTTON 10%NYLON
ST11C834-01	FABRIC COTTON 7 OZ/LINING 4 OZ FR
	FABRIC NOMEX/ZEPEL COATED
ST11D057	FABRIC POLYESTER E-1438
ST11D057-01	FABRIC POLYESTER NON-WOVEN
ST11D126-01	FABRIC COTTON/DACRON
	FABRIC UTOPIA STYLE #540982
ST11D128-01	WEBBING POLYESTER 1749
ST11D587-01	FABRIC DACRON 15292
ST11G052-01	FABRIC KEVLAR/NOMEX STYLE 145
ST11K113-01	FABRIC KEVLAR 152 KNIT
ST11K580-02	FABRIC KEVLAR STYLE FDI043
ST11K609/ILC	FABRIC LYCRA SPANDEX
ST11K742	FABRIC KELVAR 29
ST11L127-03	LABEL IDENTIFICATION 126 FABRIC
ST11L895-01	LABEL KRYLON ACRYLIC SPRAY-ON
ST11M039	FABRIC MARQUISETTE NYLON N-44
	SCREEN POLYESTER/PVC COATED MESH
ST11N054-02	FABRIC HT-10-41 NOMEX
	FABRIC NOMEX 2PLY
	FABRIC NOMEX 2PLY/FELT-1PLY
ST11N1018-01	FABRIC SPANDEX 90221/FIN 1635
ST11N105	FABRIC NOMEX 2PLY/FELT-1PLY
ST11N117-02	FABRIC MULTI FIL G1106-80MZL
ST11N117-04	FABRIC SPANDEX NYLON
ST11N1264-13	ZIPPER BRASS/NYLON/MYLAR
ST11N142-01	FABRIC NYLON A2634/B 3.8 OZ
ST11N1945 CLOTH	GLOVE CLOTH NOMEX RTV 157 GREEN
ST11N307-01	FABRIC NOMEX HF9254 3.2 OZ
ST11N593-01	FABRIC NYLON RIPSTOP UNCOATED
ST11N701-01	FABRIC NOMEX/ZEPEL COATED
	INK JUSTRITE INDELIBLE
ST11P759-01	FABRIC POLYESTER KNIT
ST11T391-01	FABRIC T162-42
ST11T614-01	FABRIC 6007-1-1-54 HEAVY WT
ST12B771-01/ILC	FABRIC POLYESTER URETHANE COATED
ST12B771-02/ILC	FABRIC POLYESTER URETHANE COATED
ST12D733-01	FABRIC NYLON DACRON COATED
ST12N083-01	FABRIC NEOPRENE RIPSTOP COATED
ST12N084-01	CONFIG/SEE 20406/20579
	FABRIC NOMEX WITH ZEPEL/ARMALON/URETHANE COATED NY
	FABRIC NOMEX/ARMALON/URETHANE COATED NY
	FABRIC NOMEX/URETHANE COATED NYLON B

SPECIFICATION	DESIGNATION
ST12N735-01/ILC	FABRIC NYLON/NEOPRENE COATED
ST12N758-01	FABRIC NYLON URETHANE COATED
ST12NO84-01	FABRIC NYLON 6611 OXFORD YELLOW
ST12P579-1	FABRIC BIAS PLY COATED
ST12T168-01	FABRIC TEFLON T-83-54
ST12W044-01	TAPE LOOP-TAPE KEVLAR 1759
ST13D1162-01	TAPE FABRIC C516 VINYL COATED
ST13E813-01	BRAID ELASTIC POLYESTER
ST13F074-01	TAPE TEFLON PATTERN 2338
ST13H819-02	FASTENER VELCRO POLYESTER HOOK 1 INCH
ST13K101-03	WEBBING KEVLAR FRL-S-196
ST13L818-07	FASTENER VELCRO NOMEX LOOP 1 INCH
ST13N062	THREAD NYLON (ALL TYPES)
ST13N070-01	WEBBING NYLON 7774
ST13N072-01	TAPE NYLON 6707
ST13N613/ILC	WEBBING POLYESTER ELASTIC
ST13N868-01	WEBBING NOMEX TAPE
ST13N868-02	WEBBING NOMEX TAPE
ST13P133-01	TAPE POLYESTER LOOP 2297
ST13P707-01	TAPE LOOP-TAPE GORTEX
ST13T061-01	THREAD TEFLON S302 SIZE B
ST13T1193-1	TAPE TEFLON TY10 SILICONE
ST13T132-01	TAPE TFE
ST13T1393	TAPE SCOTCH 666 PVC ACRYLIC ADHESVIE
ST13T1931-01	TAPE FASTAPE A PS
ST13W044-01	TAPE LOOP-TAPE KEVLAR 2176
ST13W128-05	WEBBING POLYESTER 1754
ST13W619-01	WEBBING NYLON 7774
ST13W702	TAPE ELASTIC 14738P/B8209W
ST13WO42-03	WEBBING KEVLAR 1758
ST14C671-05	CORD DACRON BRAIDED TROLL 70LB
ST14C737-02	CORD NYLON G1008 1/8 DIA
ST14C953-01	CORD PBI STYLE S121
ST14G730	LACING TAPE GORTEX
	LACING TAPE GORTEX .062 DIA
ST14K963	CORD KEVLAR B275
ST14N099-01	YARN STYLE 7511
ST14N162	LINE CASTING WHITE GHOST NYLON
ST14N162-01	CORD NYLON
ST14N331-01	CORD NOMEX BRAIDED
ST14P134	LACING TAPE POLYESTER 2298
ST14P134-01	CORD POLYESTER .0625 NATURAL
	LACING TAPE POLYESTER 2298
ST14P134-02	LACING TAPE BLACK
ST14P134-03	LACING TAPE POLYESTER RED
ST14P135-02	THREAD POLYESTER SIZE E
ST15G068	THREAD GORE-TEX S012T3 PTFE
ST15K103	THREAD KEVLAR B132
ST15K103-01	THREAD KEVLAR
ST15N047	THREAD NYLON (ALL TYPES)
ST15N047-01	THREAD NYLON (ALL TYPES)
ST15N055-01	THREAD NYLON NON-MELTING NOMEX
ST15N361	THREAD NYLON
ST15N361-01	THREAD NYLON VT295 SIZE E
ST15N814-02	THREAD NOMEX

MSFC-HDBK-527 REV F 9999942 0006675 6

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
ST15N871-01	THREAD NYLON SIZE E OLIVE DRAB
ST15P1252-01	THREAD POLYESTER LOFTEX T16
ST15P135-16	THREAD POLYESTER BLACK FF
ST15P135-17	THREAD POLYESTER GOLD
ST15T157-01	TUBING LATEX RUBBER
ST16F599	ZIPPER TALON 705-19 NYLON/BRASS
ST16N112-06	ZIPPER TALON 705-19 NYLON/BRASS
ST16N1264-10	ZIPPER 32" 5283-021B-4A40-0030
ST16T125-01	FILM TUFTANE 410 POLYURETHANE
ST16Z1838-01ILC	ZIPPER NYLON CHAIN 10VF
ST17N060	FASTENER VELCRO NYLON HOOK 65 BACKING 0199
ST17N060-03	FASTENER VELCRO NYLON HOOK 2 INCH
ST17N064-02	FASTENER VELCRO NYLON LOOP V22-90-W48 BACKING URETHANE FOAM
ST17N080-01	FASTENER VELCRO NOMEX HOOK 0.75 INCH
ST17N080-02	FASTENER VELCRO NOMEX LOOP 0.75 INCH
ST17P286-01	TISSUE DRY AND POLISHING
ST180-12-16B	CONNECTOR CONTACT 7219
ST18N822-02	RUBBER NEOPRENE
ST18R131	INK TYPEWRITER RIBBON
ST18T051	TUBING POLYURETHANE NOC
ST18T070-01	SLEEVING DACRON WOVEN FABRIC
ST18T1201-02	TUBING EVA ETHYLENE VINYL
ST18T1241-02	TUBING SILICONE RX50 SILASTIC
ST18T1242-02	TUBING ESTANE
ST19K103-01	THREAD KEVLAR
ST20 P674-01	INK SHARPIE PEN 59
ST20M852-01	BATTERY DURACELL HG RM12R 1.35
ST20P1176-01	CONNECTOR PLIERS UTICA 529
ST20P623-01	INK PM39 BLACK
ST20P677-01	MOLD COMPOUND URETHANE VL422M2
ST20T1013-06	HAMMER BALLPEEN P/N BP-N-4A
ST20T1013-62	HANDLE DRIVER F40A
ST20T1013-63	HANDLE DRIVER F50
ST20T1013-65	DRIVER IMPACT PIT-120
ST20T1013-66	HAMMER BALLPEEN P/N BP-N-4A
ST24P156-01	CONNECTOR POLYPROPYLENE #6151
ST29T1839-01	TUBING SILICONE RX50 SILASTIC
ST30A073-01	ADHESIVE UR1087 VINYL/URETHANE
ST30A093	ADHESIVE UR1087 VINYL/URETHANE
ST30A685-01	ADHESIVE BOSTIK 1205/B9072
ST30L682-01/ILC	ADHESIVE LOCTITE 504
ST30L682-02/ILC	ADHESIVE LOCTITE 242
ST30L682-03	ADHESIVE LOCTITE 271 THREADLOCK
ST30L682-05	ADHESIVE LOCTITE 222-41
ST30V983-02	FASTENER VELCRO ADHESIVE 45
ST318-15	RING PLASTIC ON METAL DIODE
ST31A095-01	ADHESIVE SILGRIP SR573 SILICONE ADHESIVE SILGRIP SR6573 SILICONE
ST32A094-01	ADHESIVE URETHANE 1246 A/B
ST32A971-01	ADHESIVE CHEMLOK 304
ST32R155	ADHESIVE RESIWELD 7004/5% CABOSIL
ST32R155-01	ADHESIVE RESIWELD 7004
ST32R15S	ADHESIVE RESIWELD 7004/5% CABOSIL
ST34C749	SEALANT POLYSULFIDE PR1201HT
ST34R1944 RTV	GLOVE CLOTH NOMEX RTV 157 GREEN
ST36L918-03	ADHESIVE LOCTITE 271 THREADLOCK
ST37V597-01	RUBBER FAIRPRENE 5159
ST40A859-01	LABEL KRYLON ACRYLIC SPRAY-ON
ST41F392-01	KEL-F 800 MEK/SPRAY
ST43P138-01	BLADDER URETHANE
ST44S1119-01	LEATHER SUPER SHENE FINISH 2002
ST44S1120-01	SHOE SPRAY BLACK 317
ST46C1155	COATING SILICONE VESTAR Q9-6503
ST47P089	COATING CHEMGLAZE 9924 A/B
ST47P122-01	COATING SS4155 SILANE
ST47P892	COATING QUICK 65918
ST51B970-01	LUBE GREASE BRAYCO 815Z FLUORINATED
ST51F324	LUBE OIL KRYTOX 143AC
ST53P739	POWDER BIOSORB B210
ST5M1298-16R2U0	WIRE ELEC 16 AWG CABLE
ST61F087-03	FILM POLYURETHANE HITUFF MP1880
ST61N1598-07	SPONGE RUBBER NEOPRENE CLOSED CELL KNIT
ST61P774-01	FILM POLYURETHANE 10 MIL
ST61P774-02	FILM POLYURETHANE 5 MIL
ST61T125-03	FILM TUFTANE 410 POLYURETHANE
ST61V776	RUBBER VITON SHORE A
ST62N 745/ILC	NYLON 6/6 ZYTEL 101
ST63R1670-05	RUBBER LATEX DENTAL DAM
ST63R1670-11	RUBBER LATEX DENTAL DAM
ST64X366-01	ANTI-FOG SOLUTION P/N 350AF
ST65E1214-01	FILM RUCOTHANE CO-A5069 POLYURETHANE
ST65E1214-02	RUBBER POLYURETHANE RUCOTHANE 5154 WITH COTTON FLOC/RED PIGMENT
ST65U091-03	FILM POLYURETHANE GLOVE BLADDER
ST65U091-06	FILM POLYURETHANE GLOVE BLADDER
ST65U092	COATING HELASTIC 25GD102
ST65U092-01	COATING HELASTIC 25GD102
ST65U092-03	COATING IMPREGNANT GLOVE POLYURETHANE
ST65U092-04	COATING IMPREGNANT GLOVE POLYURETHANE
ST65U092-05	FILM POLYURETHANE GLOVE BLADDER
ST65U092-06	COATING POLYURETHANE PLENUM FILM
ST65U092-07	COATING POLYURETHANE PLENUM FILM
ST65U1244-02	COATING HELASTIC X768 POLYURETHANE
ST65U1244-03	COATING HELASTIC X768 POLYURETHANE
ST65U1244-04	COATING HELASTIC X768 POLYURETHANE
ST65U1244-05	COATING HELASTIC X768 POLYURETHANE
ST67F620-03	INSULATION FOAM OMALON 3
ST67F636-02	SPONGE RUBBER SILICONE
ST67L073-01	SPONGE RUBBER LATEX KOYLON
ST67N159	SPONGE RUBBER NEOPRENE STY36-2V 40LB
ST68S598-01	RUBBER SILICONE RTV 615
ST805624-01	INK MARKING 44
ST80C763	ADHESIVE RESIWELD 7004/5% CABOSIL
ST80C765-01	MARKING CRAYON 900 GRAPHITE BLK
ST80C765-02	MARKING CRAYON 900 YELLOW
ST80C783	ADHESIVE RESIWELD 7004/5% CABOSIL
ST80C78701	RELEASE AGENT X-AIR 4N002
ST80C965-03	MARKING CRAYON 904 CARBON BLK
ST80M893-01	INK JUSTRITE INDELIBLE

MSFC-HDBK-527 REV F 9999942 0006676 8

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
ST30P764-01	POWDER 8804 STAMPING BLUE
ST30S589	SANITIZER AMMONIUM STERICIDE
ST30S589-01	SANITIZER AMMONIUM STERICIDE
	SOLUTION 12% STERICIDE
ST90S756-01	INK BIC AF69
ST91N548-01/ILC	ADHESIVE HYLENE M50
ST90M078-01	TAPE MYLAR PS ADHESIVE
ST90R1356-01	RUBBER SILICONE 'E'
ST90T714-01	MOLD COMPOUND GEON
ST91P653-01	PLASTIC SHEET ABS BLACK
ST91P867-01	FILM POLYETHYLENE
ST925621-01	RUBBER SILICONE MEDICAL GRADE
ST92F129-01	FILM SARAN 8 CLEAR
ST92M048	FILM MYLAR ALUMINIZED
ST92M048-01	FILM MYLAR ALUMINIZED
ST92M048.01	FILM MYLAR ALUMINIZED
ST92M059	INSULATION MYLAR ALUMINIZED TYPE 2
ST92M059-01	FILM MYLAR ALUMINIZED
ST92M954-01	FILM MYLAR MIRROR REFLECT
ST92T837-01	FILM TEFLON TFE
ST94G086-01	LAMIN EPOXY/GLASS CORDOPREG E293
ST95V939-01	VESPEL KS105
STD AN 229	ZIPPER NOMEX VF106
STL-1000-650	PASTE SILVER SOLDER
STM 0051-01	RUBBER SILICONE RTV 566
STM 0069-12	TUBING ELEC PTFE HST DUAL WALL
STM 0519	TUBING KYNAR CONVOLUTED BLACK
STM 0532-01	COATING POLYURETHANE PR1060D
STM 0532-02	COATING POLYURETHANE PR1568M
STM 0685	COATING 515-700/910-704 463-3-100/118
	COATING 821-331 POLYURETHANE FLAT WHITE
	COATING 821-425/515-700 PRIMER
STM 0695-01	TAPE ALUMINIZED KAPTON 14162-51
STM 0695-03	TAPE POLYIMIDE PS
STM 0706-02	RUBBER SILICONE RTV 566
STM 144	TUBING TEFLON TFE HST
STM 145	TUBING FEP 100 HST
	TUBING TEFLON FEP HST
STM 203	TUBING FIBERGLASS
	TUBING FIBERGLASS "S"
	TUBING FIBERGLASS S1600-H
	TUBING FIBERGLASS SLV 1200
STM 235	TUBING TEFLON FEP HST
STM 250	TUBING PTFE NON-HEAT SHRINK
STM 6372439	WIRE ELEC TEFLON TFE
STM A567	INSULATION BLANKET AU/AL COATED
	INSULATION BLANKET AU/AU COATED POLYIMIDE
STM A568	INSULATION BLANKET AU/AL COATED
	INSULATION BLANKET AU/AU COATED POLYIMIDE
STM A569	INSULATION BLANKET AU/AL COATED
STM-0532-01	COATING POLYURETHANE PR1060D
STM-0564-020302	CLAMP RL5033/CUSHION L32171
	CLAMP ST253/CUSH MOSITES 1059
STM-E-2202B	WIRE ELEC TEFLON TFE
STM-E-300	CABLE ELEC TFE/BEN-HAR GLUE

SPECIFICATION	DESIGNATION
STM-E-300	CABLE ELEC TFE/BEN-HAR SLEEVE
	CABLE ELEC TFE/VARGLAS SLEEVE
	WIRE ELEC TEFLON TFE
STM-E-300-1	CABLE ELEC PTFE WITH SHEATH TAPE
	CABLE ELEC TFE/VARGLAS SLEEVE
	WIRE ELEC TEFLON TFE
STM-E-646	WIRE ELEC TFE/GLASS WARP
STM-E-658	WIRE ELEC FEP
	WIRE ELEC TEFLON TFE
STM-E-659	WIRE ELEC FEP/POLYIMIDE TAPE
STM-E-741	WIRE ELEC FEP/POLYIMIDE TAPE
	WIRE ELEC WRAPPED IN P2650 SILICONE TAPE
STM-E-921	WIRE ELEC TFE/ML ENAMEL
STM-E300-1	HARNESS TENSOLITE ASSEMBLY 20AWC
STM-F-144	TUBING PTFE HST
	TUBING PTFE SHRINKABLE
STM-F-203	TUBING FIBERGLASS SLV 1200
	WIRE ELEC VARGLASS SLEEVE 20AWG
STM-F-250	TUBING PTFE NON-HEAT SHRINK
STM-F-416	LACING TAPE F416 TEFLON COATED
	LACING TAPE PTFE/GLASS
STM-F-4177	LACING TAPE PTFE/GLASS
STM-J-676	TAPE TEFLON PTFE ANTISEIZE
STM-K-776	LAMIN EPOXY/GLASS VIBRATION DAMPER
STM-K-796	COMPOSITE GLASS/AL/934 RESIN
STM-K776 T2	LAMIN EPOXY/GLASS/SOLITHANE COATED
STM-L-744	INSULATION FOAM PDL4034-2.5/ SEALED WITH DAPCOSEAL 2030
	INSULATION FOAM PDL4034/COATED WITH FRL
STM-M-173	TAPE P69 PS
STM-Y-824	COMPOUND LEAK TEST
STM-Y-985	INSULATION BLANKET AU/AL COATED
	INSULATION BLANKET AU/AU COATED POLYIMIDE
STM0069-12	TUBING ELEC PTFE HST DUAL WALL
STM0519-020402	TUBING THERMOFIT 218 HST CONVLEX
STM0530-03	LAMIN FIBERITE MXB5004/1581
STM0532-01	COATING POLYURETHANE PR1060D
STM0564-020302	RUBBER FLUOREL 5033
STM0599-09	TAPE 003004SX1014 COLOR 4 ANODIZED ALUMINUM WITH PS ACRYLIC ADHESIVE
STM0685-01	COATING 463-3-33 TC/515-700 PRIMER
	COATING 515-700/910-704 CATALYST
	COATING 528-305/515-700 PRIMER
STM06910020202	FILM POLYIMIDE/ALUMINUM/NOMEX/SCRIM
STM0699-01	RUBBER VITON E60C/HT426 NOMEX
STM0710-01	ADHESIVE M-BOND 600
STM0711-01	TAPE P213 GLASS ACRYLIC ADHESIVE
STM0737	ADHESIVE EA9330 EPOXY
STME 643	WIRE ELEC TEFLON TFE
STME 7192009	WIRE ELEC TEFLON TFE
STO125LB0001	COATING LADICOTE COMPOSITE
STP-30151	COATING POLYAMIDE WITH CHEMGLAZE Z306
STP-30169	COATING EPOXY POLAMIDE WITH POLYURETHANE OVERCOAT
	COATING EPOXY POLYAMIDE ON STAINLESS STEEL

MSFC-HDBK-527 REV F 9999942 0006677 T

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
STP-30170	COATING EPOXY POLYAMIDE ON STAINLESS STEEL
STP135-18	THREAD POLYESTER STEEL SIZE F
STRS-2738	SILICONE RUBBER, TR9904
STSV 438	CABLE TIES TEFZEL TY-RAP TYZ
STSV09-9	CORD KEVLAR 29 73457
STSV091-9	CORD KEVLAR 29 73457
STSV107-3	LACING TAPE TG-30 20AWG
STSV128 S4	TAPE G407810 VACUUM DEPOSITED ALUMINUM 1 MIL KAPTON WITH 1 MIL SILICONE ADHESIVE
STW 3431	ADHESIVE PRESSURE SENSITIVE
STW 5-2721	ADHESIVE CHEMLOK 234B
STW-2830	ADHESIVE RUBBER NBR/MEK
STW1-2808	EXPLOSIVE RDX/LSC
STW1-3134	TUBING POLYURETHANE CABLE JACKET
STW1-3353A	RUBBER FLUOROCARBON
STW4-2563	TAPE BLASTAPE 2 STYLE MX4703
STW4-2621	RUBBER NBR INSULATION
STW4-2700	INSULATION CORK AB600
STW4-2736	RUBBER NEOPRENE/SILICONE FILL
STW4-2748	LAMIN PHENOLIC/COTTON
STW4-2857	RUBBER NYLON REINFORCED
STW4-3259:COATING	INSULATION FOAM CPR1061 COATED WITH ALBI-COTE FRL WITH COATED SEMICIRCLE
STW4-3259:CTNG	INSULATION FOAM CPR1061 WITH ALBI COTE COATING
STW5 2930 T2	POTTING COMPOUND EA937
STW5-2643	RUBBER TR3005
STW5-2649	FABRIC CARBON PHENOLIC ABLATIVE
STW5-2650	COATING DC 93-104 SILICONE
STW5-2651	FABRIC MXB6020/FM5755 GLASS PHENOLIC
STW5-2652	FABRIC MX2600/FM5504 SILICA PHENOLIC
STW5-2655	ADHESIVE CERAMIC TYCEMENT UF3206
STW5-2667	ABLATIVE COMPOUND PHENOLIC/SILICONE
STW5-2673	PROPELLANT TPH1154
STW5-2676	PROPELLANT LINER UF2137
STW5-2678	SEALANT UF3195
STW5-2683	PROPELLANT TPH1148
STW5-2687	ABLATIVE C/FIB FIBERITE MXC313
STW5-2701	COATING FUNGICIDAL
STW5-2712	ADHESIVE CHEMLOK 233
STW5-2803	ADHESIVE S2288
STW5-2820	ADHESIVE EPON 812
STW5-2823	LUBE O-RING
STW5-2835	RUBBER RTV 88
STW5-2842	ADHESIVE EPOXYLITE 8822
STW5-2847	PUTTY ZINC CHROMATE 3992
STW5-2858	COATING SS4171 SILANE
STW5-2868	RUBBER NEOPRENE/CARBON FIBER
STW5-2870	ADHESIVE CHEMLOK
STW5-2931	ADHESIVE EA946
STW5-2939	COATING TURCO T6109 WHITE
STW5-2942	LUBE GREASE HD CALCIUM 2
STW5-2970	ADHESIVE M-BOND 200
STW5-2975	POTTING COMPOUND EA919 UF3280 CORK
STW5-2983	COATING HYPALON/GACOFLEX H2200 WHITE
STW5-2994	COATING HYPALON/GACOFLEX HFR2200
STW5-2997	SEALANT UF3177
STW5-2998	SEALANT UF3119
STW5-3180	INSULATION FOAM CPR920-9-2/HFR2200 PS
STW5-3180:FOAM	INSULATION FOAM CPR1061 COATED WITH ALBI-COTE FRL WITH COATED SEMICIRCLE
	INSULATION FOAM CPR1061 WITH ALBI COTE COATING
STW5-3479	ADHESIVE PRESSURE SENSITIVE
STYLE 26435	FABRIC KEVLAR 49
STYLE DPB-38-37	FABRIC KELVAR 29
STYLE N202	GLOVE COMFORT NYLON/TRICOT
SV3148 THINNER	COATING NEXTEL 900 WHITE
SV755622-4	CABLE ASSEMBLY NYLON/GLASS
SV767701	COMPOSITE KEVLAR/EPOXY WRAP
SV771777/8/9	HARNESS ASSEMBLY NOMEX BRAIDED 200 DENIER COVER
SV772104-1	INK DURAGRAPH B20082 AL RED
SV777202-1	HOSE SILICONE/PBI POS BREATHER
SV778533-1	VALVE NON-REBREATHER
SV8507 TYC	ECCOGEL 1265/EPOXY
SVHS 10077	INK BLADDER MARKING URETHANE
SVHS 10087	FILM RUCOTHANE CO-A769 POLYURETHANE
SVHS 10091	ADHESIVE BOSTIK 7376
SVHS 7302	COATING D4D THERMAL CONTROL ALUMINUM/SILICONE
SVHS 7873	COATING PEDIGREE 923 EPOXY VARNISH
SVHS 7873T1	COATING POLYURETHANE (ESTER)
SVHS 7890	COATING NA7509-V73/NA7486-V66 PLU
SVHS 7890 APP 2	COATING EPICEL 3 EPOXY/CURE AGENT U
SVHS 798T2	LAMIN EPOXY/GLASS
SVHS 8090T15	LAMIN EPOXY/CAB-O-SIL
SVHS 8091T10	LAMIN EPOXY/GLASS EPON APCO 434/SONITE 41
SVHS 8091T12	LAMIN POLYESTER/GLASS HETRON 92
SVHS 8091T5	COATING APCO 434/SONITE 41 EPOXY
SVHS 8091T6	ADHESIVE EPON 815/DTA/PHENOLIC F
SVHS 8091T7	ADHESIVE EPON 815/DTA
SVHS 8091T8	LAMIN/EPOXY/GLASS EPON 815/GLASS 7781/DTA
SVHS 8091T9	LAMIN/EPOXY/GLASS/EPON 815/GLASS 112/DTA
SVHS 8507TB	ECCOGEL 1265/EPOXY
SVHS 8509	RUBBER CHLOROPRENE NOC
SVHS 8511	COATING SILICONE SR80 RESIN
SVHS 8513	COATING DIMETCOTE 3/AMERCOTE 383HS
SVHS 8523	LUBE GREASE BRAYCOTE 601
SVHS 9444	BLADDER NEOPRENE 3N868 NO4/6
SVHS 9656T2	COATING EPOXY WHITE TOPCOAT WITH H2 CATALYST
	COATING WHITE EPOXY/H2
SWM-109	TEFLON TFE VIRGIN
TBFH22950-73	CONNECTOR ELECTRICAL
TB0130-001	LAMIN EPOXY/GRAPHITE F263
	LAMIN THORNEL 300/934 GRAPHITE/EPOXY
TB0130-302	LAMIN EPOXY/GLASS CE9000
TC MIL-C-83286	COATING POLYIMIDE EPOXY YELLOW TC
TF70-R3A-01A	RUBBER VITON FLUID RESISTANT

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006678 1

SPECIFICATION	DESIGNATION
TG-4060	ARMALON
T0601/T0930	ADHESIVE EPOXY R82038/HD3475
T0607 & V0422	INK WORNOWINK M-9-N/100 PARTS BY WEIGHT OF INK BLENDED WITH 4.9 PARTS BY WEIGHT OF C ATALYST
T0811/A0429	ADHESIVE ARMSTRONG A8-4219/H2-3404 EPOXY
TP-H-3282C	PROPELLANT SOLID
TT-E-489	COATING ALKYD GLOSS ENAMEL 12246
	COATING ALKYD GLOSS ENAMEL YELLOW
TT-E-489CA	COATING ALKYD GLOSS ENAMEL 12246
TT-E-516	COATING ENAMEL LUSTERLESS STYRENE ALKYD
TT-E-527	COATING ENAMEL GREY
TT-E-527 COMP G	COATING 36231 ALKYD ENAMEL
TT-E-529	COATING ENAMEL SEMIGLOSS GRAY
TT-E-529C1A	COATING GREY ENAMEL/PRIMER
TT-F-325A	COATING LACQUER STICK BLACK
TT-I-1795T1	INK 73X
	INK MARKING STENCIL
TT-I-1795T3	INK STENCIL BLACK
TT-L-20A	COATING L496A-66/37038 CAM LACQURE
TT-L-32	COATING PT111 LACQUER
	LACQUER CELLULOSE NITRATE YELLOW
TT-L-50T2	COATING LACQUER ACRYLIC
TT-P-1757	COATING ZINC CHROMATE
TT-P-19	COATING ACRYLIC EMUL-EXT-WHITE
TU-33X	INSULATION FOAM TU28 URETHANE
	INSULATION FOAM TU32 URETHANE
TX-2006-21B	INSULATION FOAM TX39 URETHANE
	INSULATION FOAM TX43 URETHANE
UF-3262	ADHESIVE EA946
UL TYPE 94HF1	INSULATION URETHANE UNIFOAM S82N
USB-MS-1001	CORK COMPOSITION
USB-MS-1002	INSULATION MSA-1
USB-MS-1004	LAMIN PHENOLIC/S-GLASS CLOTH
USB-MS-1005	CORK B STAGE
USB-MS-1009	FABRIC NYLON FLAME RETARD
USB-MS-2001	INSULATION MTA-1
USB-MS-2003	INSULATION MTA-2
USB-MS-2004	CORK COMPOUND K5NA
USB-MS-2005	RUBBER SILICONE RTV 855
USB-MS-5001	COATING RUBBER HYPALON NOC
USB-MS-5002	COATING HYPALON/GACOFLEX HFR2200
USB-MS-9002	FILLER MATERIAL ECCOSPHERES SI
USBI10753-0032	ABLATOR BTA BOOSTER TROWELLABLE/EC2216/ GLASS SPHERE/CORK
USBI99600-0002	ADHESIVE BOSTIK 1008
USBI99600-0010	RUBBER SILICONE RTV 345
USBI99605-0010	TAPE MX4703-2
USBI99605-0015	TAPE 898
USBI99608-0103	INSULATION CEMA FIBER 111
USBI99611-0000	ETCHANT-BONDAIV S16943
USBI99621-0001	SEALANT TORQUE F900
UU-P-258	PAPER INDEX LONG GRAIN PULP WOOD FIBER MATERIAL
V-F-106 AN 229	ZIPPER NOMEX/COATING VITON B50

SPECIFICATION	DESIGNATION
V-T-276	THREAD COTTON 2 CORE
	THREAD COTTON CORD ALL TYPES
V-T-285.T1	THREAD POLYESTER F
V-T-295	THREAD NYLON
V070-060068	MULTI-LAYERED INSULATION KAPTON/NOMEX/AU/ TG 15000
V0707&V0630	ADHESIVE EPOXY PATCH KIT 0151 CLEAR A/B
V762-363817	MULTI-LAYERED INSULATION KAPTON/NOMEX/AU/ TG 15000
VV-P-236	LUBE GREASE BRAYCOTE 236
VZ-5151-420	RUBBER FAIRPRENE 5159
WIT-280RM	FABRIC NOMEX HT-45-55 WITH DC3140 RTV COATING ON ONE EDGE
	FABRIC NOMEX HT-45-55 WITH DYE-AQUA-SET TEXTILE INK WITH DC3140 RTV COATING ON ONE EDGE
WIT-304RM	FABRIC NOMEX HT-45-55 WITH DC3140 RTV COATING ON ONE EDGE
	FABRIC NOMEX HT-45-55 WITH DYE-AQUA-SET TEXTILE INK WITH DC3140 RTV COATING ON ONE EDGE
WIT-412RM	FABRIC NOMEX HT-45-55 WITH DC3140 RTV COATING ON ONE EDGE
	FABRIC NOMEX HT-45-55 WITH DYE-AQUA-SET TEXTILE INK WITH DC3140 RTV COATING ON ONE EDGE
WIT-482RM	FABRIC NOMEX HT-45-55 WITH DC3140 RTV COATING ON ONE EDGE
	FABRIC NOMEX HT-45-55 WITH DYE-AQUA-SET TEXTILE INK WITH DC3140 RTV COATING ON ONE EDGE
WIT-541RM	FABRIC NOMEX HT-45-55 WITH DC3140 RTV COATING ON ONE EDGE
	FABRIC NOMEX HT-45-55 WITH DYE-AQUA-SET TEXTILE INK WITH DC3140 RTV COATING ON ONE EDGE
ZZ-R-765	FABRIC SILICONE RUBBER/ARAMID
	GASKET SILICONE NOMEX HT 46-45
	HOSE URINAL SILICONE RUBBER/WIRE
	RUBBER SILICONE 0117 DACRON REINFORCED
	RUBBER SILICONE 77C 12640
	RUBBER SILICONE 92276
	RUBBER SILICONE HT 2-80 SHOCK ISOLATOR
	RUBBER SILICONE NOC ZZ-R-765
	RUBBER SILICONE RTV 560 EPOXY/GLASS
	RUBBER SILICONE S317
	RUBBER SILICONE/ALUMINUM/DC282
	RUBBER VULCON CL 2 GR 40
ZZ-R-765 CL 1A & 1B GR 40	RUBBER SILICONE CL 1A & 1B GR 40
ZZ-R-765 CL 1A & 1B GR 50	RUBBER SILICONE CL 1A & 1B GR 50
ZZ-R-765 CL 1A & 1B GR 60	RUBBER SILICONE CL 1A & 1B GR 60

MSFC-HDBK-527 REV F 9999942 0006679 3

Information Handling Services, 2000

SPECIFICATION	DESIGNATION
ZZ-R-765 CL 1A & 1B GR 70	RUBBER SILICONE CL 1A & 1B GR 70
ZZ-R-765 CL 1B GR 50	FABRIC GLASS/SILICONE
	GASKET MATERIAL RUBBER SILICONE/NOMEX
	GASKET MATERIAL X106 NOMEX/RUBBER
ZZ-R-765 CL 1B GR 80	RUBBER SILICONE CL 1A & 1B GR 80
ZZ-R-765 CL 2 GR 50	GASKET POLASHEET SILICONE/MONEL
ZZ-R-765 CL 2A	RUBBER SILICONE 2850R
ZZ-R-765 CL 2A & 2B GR 25	RUBBER SILICONE CL 2A & 2B GR 25
ZZ-R-765 CL 2A & 2B GR 40	RUBBER SILICONE CL 2A & 2B GR 40
ZZ-R-765 CL 2A & 2B GR 50	RUBBER SILICONE CL 2A & 2B GR 50
ZZ-R-765 CL 2A & 2B GR 80	RUBBER SILICONE CL 2A & 2B GR 80
	RUBBER SILICONE S614-80
ZZ-R-765 CL 2B	RUBBER SILICONE CL 2A & 2B GR 70
ZZ-R-765 CL 2B GR 50	FABRIC GLASS/SILICONE
ZZ-R-765 CL 2B GR 60	RUBBER SILICONE CL 2A & 2B GR 60
ZZ-R-765 CL 2B GR 70	RUBBER SILICONE SE4404U WITH SIO2 FILLER
ZZ-R-765 CL 2B GR 80	RUBBER SILICONE NE6071/6071
ZZ-R-765 CL 3A	RUBBER SILICONE HADBAR 3254
	RUBBER SILICONE HERCULES H564
ZZ-R-765 CL 3A GR 25	RUBBER SILICONE CL 3A GR 25
ZZ-R-765 CL 3A GR 30	GASKET MATERIAL HASKON 8099 NOMEX/RUBBER SILICONE
	RUBBER SILICONE CL 3A GR 30
ZZ-R-765 CL 3A GR 50	RUBBER SILICONE AP3004 CL 3A GR 50
ZZ-R-765 CL 3A GR 60	RUBBER SILICONE CL 3A GR 60
ZZ-R-765 CL 3B	RUBBER SILICONE H567
	SEALANT SILICONE/FEP TEFLON
ZZ-R-765 CL 3B GR 25	RUBBER SILICONE HADBAR 3250
ZZ-R-765 CL 3B GR 30	RUBBER SILICONE CL 3B GR 30
ZZ-R-765 CL 3B GR 50	FABRIC SILICONE/NYLON H565
	GASKET SILICONE 7241/KEVLAR K120
	RUBBER SILICONE CL 3B GR 50
ZZ-R-765 CL 3B GR 60	CLAMP CUSHION SILICONE/FIBERGLASS CL 3B GR 60
	RUBBER SILICONE CL 3B GR 60
ZZ-R-765 CL 3B GR 70	RUBBER SILICONE CL 3B GR 70
ZZ-R-765 CL 3B GR 80	RUBBER SILICONE CL 3B GR 80
ZZ-R-765BC3BG50	RUBBER SILICONE S899-50

MSFC-HDBK-527 REV F 9999942 0006680 T

Information Handling Services, 2000

TABLE 2C

NONMETALS BY CODE

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
00000	1,537	Z MATERIALS SHOWN ON LOWER ASY
00001	175	ADHESIVE HT424 EPOXY
00005	99	ADHESIVE EA828/VERSAMID 115 EPOXY
00007	103	ADHESIVE EA934NA EPOXY
00010	583	INK 73X
00013	707	LAMIN EPOXY/PHENOLIC M602
00016	1,471	TEFLON TFE VIRGIN
00019	783	NYLON PLASTIC
00020	519	FASTENER VELCRO NYLON HOOK AND LOOP
00030	598	INK WORNOWINK M-O-N/CAT A
00031	1,258	POTTING COMPOUND STYCAST 1090/C9
00042	360	COATING LAMINAR X500 POLYURETHANE
00065	138	ADHESIVE EPON 828/DTA EPOXY
00070	767	MOLD COMPOUND FS10 DAP
00098	730	LUBE DRY LUBECO 905 FILM
00106	749	LUBE GREASE THERMAL DC340 HS
00128	1,341	RUBBER SILICONE RTV 102
00133	1,389	SEALANT LOX-SAFE
00140	425	DELRIN 500
00145	49	ADHESIVE AZ/CAT E EPOXY
00155	1,335	RUBBER SILICONE EMS342
00172	388	COATING SS4004 SS4004 SILANE
00189	1,457	TAPE SCOTCHCAL 3650
00197	355	COATING HFA ANTIGLAR OPTICAL
00250	355	COATING HUMISEAL 1B12 ACRYLIC
00298	1,050	PLASTIC PLEXIGLASS 55
00299	419	CORD PARACHUTE NYLON
00339	961	PLASTIC LEXAN POLYCARBONATE CLEAR
00367	1,492	TUBING KYNAR RT850 HST
00385	1,445	TAPE SCOTCH 363 REFLECTIVE
00395	734	LUBE DRY PHENOLIC BINDER N350A
00440	344	COATING EC766 NITRILE/PHENOL
00468	1,514	WEBBING DACRON
00495	494	FABRIC REFRASIL C100-48 SILICA
00507	176	ADHESIVE HT424 THIXOTROPIC PASTE
00509	165	ADHESIVE FILM FM123-2 FILM EPOXY
00511		DELETED SEE 00001
00515	744	LUBE GREASE KRYTOX 240AC
00528		DELETED SEE 05084
00530	310	COATING 401 SERIES VELVET POLYESTER
00543	1,450	TAPE SCOTCH 61 TFE/SILICONE PS
00551	1,348	RUBBER SILICONE RTV 511/SS4155
00552	356	COATING HYPALON 150W-8
00573	501	FABRIC TFE GLASS TG 4060
00578	1,500	TUBING TEFLON FEP HST
00591	105	ADHESIVE EASTMAN 901
00597	733	LUBE DRY NPI14
00633	288	BRAKE MATERIAL R740 BTG
00649	1,469	TEFLON FEP
00666	337	COATING CONVERSION CHROMATE
00701	544	FILM MYLAR POLYESTER
00708	165	ADHESIVE FILM FM1000 POLYAMIDE
00718	1,432	TAPE MYSTIK 7402 ALUMINUM SILICONE ADHESIVE
00755	278	ADHESIVE X1160 PS
00763	768	MOLD COMPOUND M2840 MELAMINE
00777	452	FABRIC FIBERGLASS STYLE 7628
00880	727	LUBE DRY ELECTROFILM 2306 INORGANIC
00881	728	LUBE DRY EVERLUBE 812
00895	85	ADHESIVE DC281 SILICONE WITH CATALYST
00898	85	ADHESIVE DC92-018 SILICONE
00903	754	LUBE OIL KRYTOX 143AC
00926	357	COATING INSULUBE 448 URETHANE
00934	110	ADHESIVE ECCOBOND 51/C9 EPOXY
00964	675	LACING TAPE HT-30 LOC B NOMEX
00968	365	COATING NEOPRENE LN2500A
00987	1,350	RUBBER SILICONE RTV 577/T12
01018	658	INSULATION TG15000/SILICONE/GLASS BINDER
01036	1,348	RUBBER SILICONE RTV 560 COMPOS
01039	1,348	RUBBER SILICONE RTV 560
01173	156	ADHESIVE EPOXYLITE 801/C307
01175	124	ADHESIVE EPIBOND 123/931 EPOXY
01267	532	FILM ACLAR 33F CTFE
01276	354	COATING HEA LENS INORGANIC
01336	564	GERMICIDE PHENYLPHENOL PROPYL
01342	539	FILM KAPTON POLYIMIDE
01455	1,283	RUBBER EPR E515-80
01596	1,478	THREAD NYLON NON-MELTING NOMEX
01597	484	FABRIC NYLON/NEOPRENE COATED
01602	448	FABRIC DUCK GREEN
01716	712	LAMIN MELAMINE/GLASS G9-818
01728	687	LAMIN COTTON/PHENOLIC
01730	1,460	TAPE STOMASEAL 1522 PS
01784	1,308	RUBBER NITRILE N304-75
01811	1,323	RUBBER SILASTIC RTV 732
01838	1,361	RUBBER SILICONE SI503
01843	379	COATING PRIMER WASH
01879	718	LAMIN SYNTHANE G9 NATURAL
01883	718	LAMIN SILICONE/GLASS
01897	2	ABSORBER CO2 LITHIUM HYDROXIDE
01942	481	FABRIC NYLON
01978	682	LACING TAPE PYROLACE STFE-40B
02008	707	LAMIN F131-21 GLASS/SILICONE
02030	451	FABRIC FG104 BETA F017A FINIS
02055	322	COATING A423/T252 EPOXY
02096	383	COATING RTV 11/T12 SILICONE
02112	1,537	YARN TFE TYPE 302
02151		DELETED SEE 61407
02154	1,502	TUBING TFE/FEP TYPE WFT
02231	69	ADHESIVE CHEMLOK 205 PRIMER WITH CHEMLOK 220 TOPCOAT
02257	667	LABEL IDENTIFICATION MARKING FOIL TFE
02343	714	LAMIN PHENOLIC/PAPER
02432	715	LAMIN POLYIMIDE/GLASS
02468	360	COATING LAMINATE FLEXIBLE/ALUMINUM/H-FILM
02477	281	ARMALON XT 7XXXX
02631	1,258	POTTING COMPOUND STYCAST 1266
02638	1,334	RUBBER SILICONE DC93-072
02685	557	FLUOROCARBON RL-3540 GUM STOCK
02691	360	COATING LADICOTE COMPOSITE
02698	390	COATING TFE 1 COAT GRAY

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006682 3

MATCD	PAGE	DESIGNATION
02816	1,533	WIRE ELEC TFE/ML ENAMEL
02827	338	COATING D4375 VITON
02860	717	LAMIN SHIM/POLYESTER ADHESIVE
02882	1,404	SPONGE FLUOREL RL2060
02887	1,288	RUBBER FLUOREL 1062
02893	714	LAMIN PHENOLIC/GLASS F508 VOLAN A/7781
02897	1,433	TAPE MYSTIK 7455 ADHESIVE
02909	767	MOLD COMPOUND FIBERITE FM4030-190
02921	1,406	SPONGE RUBBER SILICONE
02945	697	LAMIN EPOXY/GLASS L-P-509 TYPE G10
02952	1,406	SPONGE RUBBER SILICONE
02955	689	LAMIN EPOXY/GLASS
02958	1,520	WEBBING NYLON TAPE
02961	1,538	ZIPPER BRASS/COTTON
02966	1,272	RUBBER BUTYL
02968	453	FABRIC FLUOREL/GLASS RL3520
02970	653	INSULATION LAMINATE E7023-1581
02976	1,339	RUBBER SILICONE NOC ZZ-R-765
02979	1,520	WEBBING NYLON FIRE/WATER PROOF
02994		DELETED SEE 60469
02997	305	CLAMP SILICONE/GLASS
03002	490	FABRIC POLYBENZIMIDAZOLE (PBI)
03022	438	FABRIC BETA/TFE COATED 95-049
03046	1,288	RUBBER FLUOREL 2231
03047	764	MOLD COMPOUND DUREZ 11864 PHENOLIC
03257	651	INSULATION GLASS FABRIC/ALUMINUM FOIL
03266	455	FABRIC GLASS/SILICONE
03280	223	ADHESIVE PR1710-1711 VITON
03285	438	FABRIC BETA YARN/TFE
03301	456	FABRIC GLASS/SILICONE
03323	1,515	WEBBING FLUOREL GLASS RL 3603
03398	341	COATING DC Z6020 SILANE
03403	457	FABRIC GLASS/TFE COATED
03422	712	LAMIN MYLAR/PROPYLENE
03428	713	LAMIN PHENOLIC/GLASS
03433	525	FASTENER VELCRO POLYESTER HOOK H549
03449	420	CORD SF429 GLASS/TFE COATED
03458	1,272	RUBBER BUTYL
03462	1,288	RUBBER FLUOREL 1066
03467	2	ABSORBER SILICA GEL
03472	1,540	ZIPPER TALON 705-19 NYLON/BRASS
03473	1,288	RUBBER FLUOREL 1079K
03484	1,349	RUBBER SILICONE RTV 566
05000	388	COATING SS4155 SILANE
05002	1,308	RUBBER NITRILE N602-7
05003	1,270	RUBBER AF-E332 EPR
05004	369	COATING PM47 PRIMER
05005	1,375	RUBBER VITON FLUID RESISTANT
05006	421	CORE HRP/HFT GLASS/PHENOLIC HC
05007	421	CORE HONEYCOMB/ALUMINUM FACE PLATES ADHESIVE BONDED
05008	454	FABRIC GLASS FOR PLASTIC LAMIN
05009	385	COATING SILICONE
05010	340	COATING DC 92-007 SILICONE
05011	1,408	SPONGE RUBBER SILICONE PD200-16 SILICONE
05012		DELETED SEE 05011
05013	642	INSULATION FOAM SILICONE RL1973
05015	388	COATING SUPER KOROPON 515-700
05016	1,481	TILE SILICA LI900
05017	1,480	TILE REI SILICA 9
05018	529	FELT SILICA FI600
05019	155	ADHESIVE EPOXY WS1183 CB5
05020	710	LAMIN HMS/X904
05021	603	INSULATION FLEX ALUMINA SILICATE
05022	396	COATING ZINC CHROMATE
05024	494	FABRIC REFRASIL C1554-48 IRISH
05026	1,407	SPONGE RUBBER SILICONE 14143
05028	705	LAMIN EPOXY/KEVLAR 570PRO/49-181 KEVLAR
05030	763	MOLD COMPOUND DAP FS5 BLACK 8000
05032	653	INSULATION MICROLITE AA1 PHEN BIND
05033		DELETED SEE 05032
05034	532	FILM AL/TEDLAR/NYLON AN16
05035	169	ADHESIVE FOAM HT424 T2
05036	111	ADHESIVE ECCOBOND 55/C9
05037	1,324	RUBBER SILICONE 14140D
05038	1,351	RUBBER SILICONE RTV 630
05039	339	COATING DC 1200 SILANE
05042	735	LUBE DRY VITROLUBE 1220
05043	1,505	TURCON/TFE
05044	733	LUBE DRY NPI425 POLYIMIDE
05045	735	LUBE DRY VACKOTE 18.07
05046	726	LUBE DRY DRILUBE 6A
05049	735	LUBE DRY VITROLUBE 2500 INORGANIC
05050	731	LUBE DRY MLR66
05051	731	LUBE DRY MICROSEAL 200-1 INORGANIC
05053	1,484	TUBING FAFTEX PTFE LINER
05054	734	LUBE DRY SPUTTERD FILMS/MOS2
05055	724	LUBE COMPOSITE DUROID 5813
05056	696	LAMIN EPOXY/GLASS FB400 GF
05057	1,511	VESPEL SP3
05058	725	LUBE COMPOSITE FEURALON AW
05059	725	LUBE COMPOSITE WDC120 TO 150
05060	725	LUBE COMPOSITE PUREBON PBM3
05061	724	LUBE COMPOSITE ELEC CONDUCT
05062	755	LUBE OIL VERSILUBE F50 SILICONE
05063	755	LUBE OIL SILICONE F6-1101
05064	739	LUBE GREASE BRAYCO 800 SERIES
05065	755	LUBE OIL SYNTHETIC BASE
05066	241	ADHESIVE SCOTCHWELD EC2216 B/A
05067	738	LUBE GREASE BRAYCO 640AC
05068	463	FABRIC KEVLAR 49/EPOXY
05069	764	MOLD COMPOUND DC302 SILICONE
05070	750	LUBE GREASE VERSILUBE G300
05071	322	COATING A934BX AMINO SILANE
05072	728	LUBE DRY EVERLUBE 811
05073	511	FASTENER VELCRO MID-TEMP NYLON HOOK AND LOOP
05074	152	ADHESIVE EPOXY PASTE CORFIL 6/5
05076	689	LAMIN EPOXY/BORON SP296
05077	538	FILM KAPTON GOLDIZED

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006683 5

MATCD	PAGE	DESIGNATION
05078	1,423	TAPE G411660 5 MIL KAPTON WITH VACUUM DEPOSITED ALUMINUM
05079	538	FILM KAPTON GOLDIZED FLOCKED
05080	461	FABRIC HT-96 NOMEX RESIN TREAT
05081	459	FABRIC HT-287-45 NOMEX
05082	446	FABRIC DACRON NET B4A
05083	438	FABRIC BETA GLASS STYLE 81677
05084	662	KEL-F CTFE UNPLASTICIZED
05085	1,431	TAPE MYSTIK 7361 KAPTON/SILICONE ADHESIVE
05086	1,432	TAPE MYSTIK 7366 KAPTON/SILICONE ADHESIVE
05087	1,466	TAPE TFE/SILICONE 503-5-DC ADHESIVE
05088	726	LUBE DRY DICRONITE DL5
05089	1,276	RUBBER CNR RESISTAZINE 88
05091	25	ADHESIVE AF143/EC3917 EPOXY FILM
05092	198	ADHESIVE METLBOND 6607 FOAM EPOXY
05093	1,527	WIRE ELEC MAGNET CL 220
05094	1,292	RUBBER FLUOROSILICONE L677-70
05095	1,291	RUBBER FLUOROSILICONE L449-65
05096	570	HALAR E-CTFE
05097	213	ADHESIVE PLASTILOCK 731 EPOXY
05098	305	CLAMP SILICON/GLASS VB
05099	1,367	RUBBER TIRE TREAD 17149
05100	739	LUBE GREASE BRAYCO 815Z FLUORINATED
05101	1,386	SEALANT CERAMIC G/I88 1/4 BAKE
05104	25	ADHESIVE AF3002 EPOXY FILM
05105	528	FELT NOMEX NON-WOVEN
05106	198	ADHESIVE METLBOND 329 EPOXY FILM
05108	225	ADHESIVE PROSEAL 828 EPOXY
05109	225	ADHESIVE PROSEAL 829 EPOXY
05110	604	INSULATION FOAM BX249N POLYURETHANE
05111	604	INSULATION FOAM BX250 VARIOUS RATIO POLYURETHANE
05112	297	CARBON/GRAPHITE BONDED
05113	742	LUBE GREASE DC11 SILICONE
05115	426	DESICCANT MOLECUL SIEVE INORG
05116	453	FABRIC FLUOREL/NYLON V16-30
05117	464	FABRIC KEVLAR/FLUOREL
05118	722	LINER FEP/KEVLAR/KAPTON/POLYES
05119	456	FABRIC GLASS/SILICONE KSF100-2
05120	456	FABRIC GLASS/SILICONE AP2363
05121	842	PLASTIC CHLORINATED POLYETHER
05122	1,509	VESPEL SP21
05123	1,508	VESPEL SP1/POLYIMIDE
05124	715	LAMIN POLYIMIDE/GLASS
05127	166	ADHESIVE FILM FM400/BR400 WITH ALUMINUM
05128	739	LUBE GREASE BRAYCOTE 3L-38RP
05129	189	ADHESIVE M-BOND 610
05130		DELETED SEE 05084
05131	714	LAMIN PHENOLIC/NYLON
05132	100	ADHESIVE EA828/VERSAMID 140 1/1BW
05133	958	PLASTIC LEXAN 9600 FR NATURAL
05135	370	COATING POLYAMIDE EPOXY
05136	718	LAMIN SILICONE/GLASS
05137	689	LAMIN EPOXY/GLASS
05138	707	LAMIN F161-173G/7781/HS8171
05139	104	ADHESIVE EA9601 EPOXY
05140	1,433	TAPE MYSTIK 7503 TFE/SILICONE ADHESIVE
05141	229	ADHESIVE RELIABOND 398 EPOXY FILM
05142	1,337	RUBBER SILICONE HARDNESS SHORE "A" 55-65
05143	1,407	SPONGE RUBBER SILICONE
05145	1,283	RUBBER EPR E688-70
05146	127	ADHESIVE EPIBOND 8287 EPOXY
05147	1,331	RUBBER SILICONE CL 1A & 1B GR 80
05148	1,332	RUBBER SILICONE CL 3B GR 50
05149	1,331	RUBBER SILICONE CL 2A & 2B GR 60
05150	1,430	TAPE MYSTIK 6402 PROPYLENE/ACRYLIC ADHESIVE
05151	1,379	RUBBER VITON PLV2000
05152	742	LUBE GREASE CASTALL 800 SILICONE
05153	553	FILM TEDLAR POLYVINYL FLUORIDE
05154	793	PEN FELT TIP F30J BLACK
05155	84	ADHESIVE DAPCOTAC 3001
05156	1,348	RUBBER SILICONE RTV 560/577
05157	561	FOAM POLYURETHANE LAST-A-FOAM
05158	736	LUBE EVERLUBE 620A
05159	310	COATING 401-B2 GRAY
05160	310	COATING 401-F1 YELLOW
05161	715	LAMIN POLYIMIDE/GLASS
05162	724	LUBE COMPOSITE BEARING KARON
05163	1,346	RUBBER SILICONE RTV 3140
05164	701	LAMIN EPOXY/GLASS/SOLITHANE COATED
05165	288	BRAKE MATERIAL R3672-7
05166	701	LAMIN EPOXY/GLASS/DC3140 COATED
05167	725	LUBE DRY 701 OXYLUBE INORGANIC
05168	280	ALCOHOL CETYL ADOL 52NF
05169	321	COATING 96-005 SILICONE
05170	1,394	SEALANT SILICONE/NOMEX HT2002
05171	1,330	RUBBER SILICONE CHOTHERM 1663
05172	1,469	TEFLON PFA 340 FLUORCARBON
05173	1,447	TAPE SCOTCH 465 ACRYLIC TRANSFER
05174	560	FLUOROLOY SL TEFLON/GRAPHITE
05175	1,386	SEALANT CARBON BASE FACE P658RC
05177	1,432	TAPE MYSTIK 7453 AL ADHESIVE
05178	110	ADHESIVE ECCOBOND 45/C15
05179	1,525	WIRE ELEC FEP/POLYIMIDE TAPE
05180	758	MARKER SLEEVING HT-TMS KYNAR/VITON HS
05181	130	ADHESIVE EPOCAST 1310 MOD-I/9223
05182	1,511	VESPEL SP211 POLYIMIDE/GRAPHITE/TFE
05183	599	INSULATION ABLATIVE EPOXY/POLYIMIDE 183K2
05184	1,344	RUBBER SILICONE RTV 168
05185	1,343	RUBBER SILICONE RTV 162
05186	653	INSULATION MICA MUSCOVITE
05187	1,468	TECHFLUORIL TFE/GRAPH CG-11
05188	568	GRAPHITE G3418 GR GTB GRAFOIL
05189	559	FLUOROLOY F TFE/CERAMIC
05190	559	FLUOROLOY B TFE/CARBON/GRAPHITE
05191	127	ADHESIVE EPIBOND X87336 EP/AG FIL
05192	102	ADHESIVE EA9309 EPOXY
05193	667	LABEL IDENTIFICATION ASSEMBLY ACRYLIC ADHESIVE/AL
05194	560	FLUOROLOY KP TFE/ECONOL
05195	1,355	RUBBER SILICONE RTV DC96-080
05196	763	MOLD COMPOUND DAP FS80/GLASS FILLED

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006684 7

MATCD	PAGE	DESIGNATION
05197	956	PLASTIC LEXAN 9034 NATURAL POLYCARBONATE
05198	306	COATING 02-GY-3 EPOXY
05199	86	ADHESIVE DC94-002 FLUOROSILICONE RUBBER
05200	1,293	RUBBER FLUOROSILICONE RTV 733
05201	316	COATING 821-331 POLYURETHANE FLAT WHITE
05202	1,504	TUBING VITON HST
05204	1,306	RUBBER NITRILE (NRB)
05205	296	CABLE TIES TEFZEL TY-RAP TYZ
05206	654	INSULATION PLENCO 1512 ALKYD/GLASS
05207	716	LAMIN POLYIMIDE/GLASS CPI2252/7781
05208	1,187	PLASTIC TORLON 4203
05209	1,066	PLASTIC POLYSULFONE P1700/P3500
05210		DELETED SEE 00649
05211	1,407	SPONGE RUBBER SILICONE
05212	1,533	WIRE ELEC TFE/ML ENAMEL
05213	411	CONNECTOR MALE-MC/ME414-0148
05214	1,392	SEALANT POLYURETHANE PRP1600
05215	631	INSULATION FOAM POLYURETHANE 711
05216	1,507	VARNISH PHENOLIC ELECTRIC INSULATION
05217	1,352	RUBBER SILICONE RTV 69-210
05218	1,245	POTTING COMPOUND CB1054 A/B EPOXY
05220	146	ADHESIVE EPOTEK H72 EPOXY
05221	723	LINER MILFLOW TEFLON
05222	722	LINER FIBRILOID NOMEX/TFE
05223	689	LAMIN EPOXY/GLASS
05224	390	COATING THERMAL CONTROL POLYURETHETHANE
05225	26	ADHESIVE AF42 EPOXY FILM
05226	241	ADHESIVE SCOTCHWELD EC2214 EPOXY
05227	1,354	RUBBER SILICONE RTV DC6-1104
05228	59	ADHESIVE C7-4248 EPOXY
05229	1,255	POTTING COMPOUND SCOTCHCAST 221
05230	1,289	RUBBER FLUOREL FC2170
05231	598	INK WORNOW 50-100R/9 WHITE
05233	1,290	RUBBER FLUOROSILICONE
05234	1,436	TAPE P252 MYLAR PS
05235	1,525	WIRE ELEC FEP/POLYIMIDE TAPE
05236	1,525	WIRE ELEC FEP WITH POLYIMIDE TAPE
05237	731	LUBE DRY MICROSEAL 100-1
05238	666	LABEL IDENTIFICATION ALUMINUM FOIL/PS ADHESIVE 467
05239	597	INK UNIGLAZE C1336 EPOXY BLACK
05240	1,420	TAPE G402600 VACUUM DEPOSITED GOLD 1 MIL KAPTON WITH MYSTIC 7361 SILICONE ADHESIVE
05241	1,429	TAPE MYLAR/ACRYLIC PS ADHESIVE
05242	766	MOLD COMPOUND EPOXY EMC 480
05244	1,388	SEALANT GRAPHITAR 39/CARBON FACE
05245	562	GASKET MAIL ASBESTOS/RUBBER
05246	355	COATING HUMISEAL 1A20 POLYURETHANE
05247	1,346	RUBBER SILICONE RTV 3145
05248	1,260	POTTING COMPOUND STYCAST 2850GT/C9
05249	367	COATING PC12-007 EPOXY
05250	1,222	PLASTIC VALOX 420 SEO POLYESTER/GLASS
05251	1,276	RUBBER COHRLASTIC 10480 SILICONE
05252	302	CERAMIC MICROCIRCUIT/INORGANIC
05253	10	ADHESIVE 5504 EPOXY/AG
05254	1,454	TAPE SCOTCH X1252 POLYESTER PS ADHESIVE
05255	1,415	TAPE DACRON
05257	1,260	POTTING COMPOUND STYCAST 2850FT/C9
05258	597	INK UNIGLAZE C1204 EPOXY
05259	241	ADHESIVE SCOTCHWELD EC1838 B/A
05260	1,250	POTTING COMPOUND E9405 EPOXY/GLASS
05261	1,436	TAPE P221 KAPTON WITH SILICONE ADHESIVE
05262	770	MOLD COMPOUND POLYESTER/GLASS MAI-60
05263	734	LUBE DRY TIOLUBE 1175 INORGANIC
05264	456	FABRIC GLASS/SILICONE
05265	352	COATING FUSECOTE 879 WITH 1000 EPOXY
05267	453	FABRIC FLUORGLAS 2812
05268	453	FABRIC FLUORGLAS 2815 TFE/SILICONE
05271	1,259	POTTING COMPOUND STYCAST 2651/C11
05272	1,332	RUBBER SILICONE CL 3A GR 30
05273	701	LAMIN EPOXY/GLASS/PHENOLIC ME449-0141
05274	463	FABRIC KEVLAR 49 T120/SILICONE 7021G
05275	1,532	WIRE ELEC TEFLON TFE
05276	1,292	RUBBER FLUOROSILICONE LS53
05277	1,292	RUBBER FLUOROSILICONE LS63
05278	1,285	RUBBER EPR N0C
05279	1,386	SEALANT CYANOSILICONE PRP711
05280	708	LAMIN FIBERFRAX T30LR (INORGANIC)
05281	560	FLUOROLOY H TFE/BORON NITRATE
05283	774	MOLD RELEASE AGENT TFE MS-122
05284	1,369	RUBBER VISTANEX MML100 BUTYL
05286	1,518	WEBBING NYLON
05287	1,305	RUBBER NITRILE
05288	1,331	RUBBER SILICONE CL 2A & 2B GR 25
05289	102	ADHESIVE EA9321 EPOXY
05290	1,389	SEALANT METASEAL 19V5M POLYESTER
05291	1,324	RUBBER SILICONE 1235-70
05292	1,425	TAPE KAPTON/ACRYLIC ADHESIVE 2342-1R
05293	1,454	TAPE SCOTCH X1205 KAPTON WITH ACRYLIC ADHESIVE
05294	1,432	TAPE MYSTIK 7367 KAPTON/ACRYLIC ADHESIVE
05295	1,465	TAPE TEMP-R-TAPE K102R
05296	674	LACING TAPE GLASS/TFE
05297	130	ADHESIVE EPOCAST 212 EPOXY
05298	782	NYLON 6/6
05299	197	ADHESIVE METASET BLUE LABEL
05300	1,113	PLASTIC RULON A TFE/GLASS
05301	341	COATING DC Q3-6500 SILICONE
05302	725	LUBE DRY DAG 206 MOS2 INORGANIC
05303	728	LUBE DRY EVERLUBE 1120-8
05304	1,511	VESPEL SP31/SP3 POLYIMIDE/MOS2
05305	1,424	TAPE INSUL PJS C100-21
05306	1,349	RUBBER SILICONE RTV 577/9811
05307	308	COATING 03-W-40 POLYURETHANE GLOSS WHITE
05308	41	ADHESIVE ARMSTRONG A18 EPOXY PASTE
05309	304	CLAMP GE2449/13407-JM-RP
05310	1,341	RUBBER SILICONE RTV 1016/9910
05311	668	LABEL IDENTIFICATION MYLAR/ALUMINUM ST66D28-1
05312	313	COATING 5078-5 CLEAR ENAMEL
05313		DELETED SEE 01978
05314	384	COATING S13 GLO THERMAL CONTROL SILICONE
05315	1,387	SEALANT EPOXY CORROSION INHIBITOR 71-Y-1

MSFC-HDBK-527 REV F 9999942 0006685 9

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
05316	715	LAMIN POLYIMIDE/GLASS
05318	1,533	WIRE ELEC TFE/ML ENAMEL
05319	1,450	TAPE SCOTCH 62 TFE/SILICONE PS ADHESIVE
05320	1,382	RUBBER VITON V77
05321	718	LAMIN THORNEL 300/934 GRAPHITE/EPOXY
05322	1,527	WIRE ELEC MAGNET CL200 TYPE K POLYESTER
05323	769	MOLD COMPOUND MARAGLASS 655/555 EPX
05324	289	BRAKE MATERIAL SD1240B
05325	421	CORE HRN-10 NOMEX/PHENOLIC
05326	1,473	TEFLON TFE/VACUUM METALIZED AL
05327	654	INSULATION PILE FIBROUS (INORGANIC)
05328	732	LUBE DRY MOLYKOTE 33
05329	751	LUBE LUBRICOID PHENOLIC/TFE
05331	451	FABRIC FIBERGLASS 2103/108 TFE
05332	1,525	WIRE ELEC FEP/POLYIMIDE TAPE
05333	1,284	RUBBER EPR E692-75
05334	563	GASKET SILICONE NOMEX HT 46-45
05335	690	LAMIN EPOXY/GLASS
05336	304	CLAMP MS21919 WDG NEOPRENE
05337	700	LAMIN EPOXY/GLASS URALANE 5750/FC721
05338	782	NYLATRON GS/GLASS FILLED NYLON
05339	1,273	RUBBER BUTYL B612-70
05340	1,278	RUBBER COHRLASTIC R10470 SILICONE
05342	1,309	RUBBER NITRILE/TFE TEFLON
05343	1,357	RUBBER SILICONE S604-70
05344	1,337	RUBBER SILICONE HARDNESS SHORE "A" 65-75
05345	1,305	RUBBER NITRILE
05346	1,258	POTTING COMPOUND STYCAST 1095/17 EPOXY
05347	362	COATING LC4 CR203 (INORGANIC)
05348	115	ADHESIVE ECCOSORB CR3 IRON/SILICONE RUBBER
05349	1,392	SEALANT SCOTCHSEAL 3950
05350	531	FILAMENT LRF205 EPOXY KEVLAR 49
05351	285	BERYLLIA (BEO 99.5%) INORGANIC
05352	300	CERAMIC ALUMINA AD-96
05353		DELETED SEE 00019
05354	173	ADHESIVE GOODRICH A1177 A/B EPOXY
05356	19	ADHESIVE ABLEBOND 783-1 EPOXY
05357	316	COATING 683-3-3Y POLYURETHANE
05358	156	ADHESIVE EPOXYLITE 801-45 EPOXY
05359	158	ADHESIVE EPOXYLITE 9653 A/B EPOXY COATING
05360	356	COATING HUMISEAL 2A72 POLYURETHANE
05361	1,345	RUBBER SILICONE RTV 3110
05362	340	COATING DC 1203 SILANE
05363	1,430	TAPE MYSTIK 6466 DOUBLE COATED ADHESIVE
05364	1,319	RUBBER SILASTIC DC675
05365	452	FABRIC FIBERGLASS/TFE 100S
05366	707	LAMIN F161-173G/7781 EPOXY/GLASS
05367	1,468	TECFLUORFIL BF-1TFE/METL OX/GL
05368	1,468	TECFLUORFIL TFE/GLASS 105
05369	764	MOLD COMPOUND DIAL 52-01 DAP
05370	751	LUBE OIL DC200 SILICONE
05371	480	FABRIC NOMEX/VITON 5713
05372	769	MOLD COMPOUND NYAFIL G10/40
05373		DELETED SEE 05164
05374	104	ADHESIVE EA956 EPOXY
05375	1,507	VARNISH SILICONE DC997
05376	1,332	RUBBER SILICONE CL 2A & 2B GR 80
05377	1,394	SEALANT SILICONE/DACRON HAVEG F717/720
05378	1,532	WIRE ELEC TEFLON PFA
05379	1,511	VESPEL SP5 POLYIMIDE/GLASS
05380	839	PLASTIC CELANEX 3310/GL/POLYE
05381	538	FILM KAPTON F150F019
05382	709	LAMIN G1065M-28-S12 WITH COPPER
05383	1,450	TAPE SCOTCH 583 ACRYLIC ADHESIVE
05384	327	COATING BR 127 EPOXY
05385	12	ADHESIVE A HMS16-1443 EPOXY
05386	450	FABRIC FAIRPRENE VT007 TFE/VITON
05387	456	FABRIC GLASS/SILICONE 562F
05388	456	FABRIC GLASS/SILICONE 564E
05389	1,325	RUBBER SILICONE 388 LB STAGE
05390	1,337	RUBBER SILICONE HB400-50
05391	435	FABRIC AL GLASS/SILICONE SRGA/0409V RD
05392	1,346	RUBBER SILICONE RTV 3144
05393	765	MOLD COMPOUND EPIALL 1960 MNRI/EPOX
05394	1,331	RUBBER SILICONE CL 2A & 2B GR 50
05395	1,282	RUBBER EPR AF-E411
05397	1,350	RUBBER SILICONE RTV 615
05398		DELETED SEE 05397
05399	1,468	TECFLUORFIL B TFE/11% METAL OX
05401		DELETED SEE 05404
05402	318	COATING 828-310 POLYURETHANE FLAT BLACK
05403	318	COATING 823-311 POLYURETHANE FLUOREL/YELLOW
05404	317	COATING 822-327 POLYURETHANE FLAT LT GRAY
05405	1,256	POTTING COMPOUND SCOTCHCAST 281 EPOXY
05406	692	LAMIN EPOXY/GLASS CE9000
05407	692	LAMIN EPOXY/GLASS AEROLAM 110/RP57
05408	302	CHARCOAL ACTIVATED NUCHAR 503
05410	1,349	RUBBER SILICONE RTV 567
05411	558	FLUOROGOLD TFE/GLASS 25%
05412	1,388	SEALANT GRAPHITE PYROLITIC
05413		DELETED SEE 05198
05414	693	LAMIN EPOXY/GLASS CE9010/120
05415	1,354	RUBBER SILICONE RTV 8112/C9891
05416	337	COATING CONVERSION BL OXIDE INORGANIC
05417	291	CABLE COAXIAL TFE/FEP
05418	1,333	RUBBER SILICONE DC8-2318U
05419	1,352	RUBBER SILICONE RTV 6508
05420	760	MERLON M40 POLYCARBONATE
05421	663	KEL-F FR-86J BETA
05422	1,335	RUBBER SILICONE EMS9300
05423	1,359	RUBBER SILICONE SE5403
05424	1,360	RUBBER SILICONE SE5601
05425	1,503	TUBING TYGON PVC
05426	1,333	RUBBER SILICONE DC CF217U
05427	1,326	RUBBER SILICONE 4300
05428	1,288	RUBBER FLUOREL 4500
05429	108	ADHESIVE EC776
05430	381	COATING PYROMARK HE
05431		DELETED SEE 05105
05432	298	CELCON WHITE

MSFC-HDBK-527 REV F 9999942 0006686 0

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
05433	1,300	RUBBER NEOPRENE
05434	1,522	WEBBING PRORYLENE
05435	236	ADHESIVE SCOTCHGRIP 1711
05436	1,405	SPONGE RUBBER NEOPRENE
05437	461	FABRIC HT-6-42/NOMEX
05438	236	ADHESIVE SCOTCHGRIP 2210
05439	70	ADHESIVE CHEMLOK 607
05440	1,326	RUBBER SILICONE 5417-7
05441	853	PLASTIC CYCOLAC GRT
05442	424	CYCOLOY KHS
05445	1,359	RUBBER SILICONE SE5211
05447	1,357	RUBBER SILICONE S614-80
05448	326	COATING BERYLCOAT D (INORGANIC)
05449	1,527	WIRE ELEC KYNAR PVF
05450	738	LUBE GREASE APIEZON L
05451	1,525	WIRE ELEC FEP
05452	687	LAMIN DUCT 02GY3 TC URETHANE 17875
05453	140	ADHESIVE EPON 828/RP7A EPOXY
05454	731	LUBE DRY LUBRIBOND A
05455	732	LUBE DRY MOLYKOTE 55M
05456	1,447	TAPE SCOTCH 48 TEFLON NO ADHESIVE
05457	765	MOLD COMPOUND E-2748 EPOXY/GLASS
05458	1,453	TAPE SCOTCH 92 SILICONE/POLYMIDE BACKING
05459	301	CERAMIC DUROCK 117
05460	796	PIEZD XTLS G1500,G1900 (INORG)
05461	1,336	RUBBER SILICONE HARDNESS SHORE "A" 35-45
05463	1,385	SEALANT 905 EPOXY
05464	1,255	POTTING COMPOUND SCOTCHCAST 247
05465	568	GRAPHITE LUBE
05466	1,361	RUBBER SILICONE SONFARREL 1151
05467	1,279	RUBBER CONSIL 861 SILICONE/CARBON FILLED
05468	1,506	VARNISH DORYL DIPHENYL OXIDE
05469	562	GASKET MATERIAL HASKON 8099 NOMEX/RUBBER SILICONE
05470	130	ADHESIVE EPOCAST 8542/38/9242 EPX
05471	1,395	SEALANT TFE/GL/MOS2 J114-7-2F-GM
05472	1,480	THREAD QUARTZ TFE COATED
05473	25	ADHESIVE AE10 EPOXY
05474	24	ADHESIVE ADX3111-1 EPOXY
05475	109	ADHESIVE ECCOBOND 285/11 EPOXY
05476	499	FABRIC TACONIC 7159-128 TEFLON
05477	233	ADHESIVE SAUEREISEN #29 INORGANIC
05478		DELETED SEE 05309
05479	461	FABRIC HT-90-40 NOMEX
05481	459	FABRIC HT-2002 ARAMID/KNIT MESH
05482	1,507	VARNISH NYLON 7-11
05483	1,458	TAPE SCOTCHLITE 3270 VINYL PS
05484	1,365	RUBBER SYNTHETIC MS35489
05485	713	LAMIN NARMCO 3203-1581 EPOXY
05486	428	DYE GREEN
05487	708	LAMIN FIBERITE MXB7701
05488	297	CARBON GRAPHITE MOLD MECH
05489	1,352	RUBBER SILICONE RTV 651
05490	583	INK 977-9
05491	1,323	RUBBER SILICONE 1000PSI HARDNESS 45 - 55
05492	43	ADHESIVE ARMSTRONG A701 EPOXY
05493	1,359	RUBBER SILICONE SE4404
05494	337	COATING CONFORMAL CONATHANE CE1155 POLYURETHANE
05495	1,114	PLASTIC RULON J TFE/GLASS
05496	383	COATING RK692 PYRE ML
05497	382	COATING REFSET L3203-6
05498	239	ADHESIVE SCOTCHWELD 2214HT
05499	1,305	RUBBER NITRILE
05501	1,472	TEFLON TFE/15% GLASS
05502	1,469	TEFLON DUROID RT4000 AL
05503	239	ADHESIVE SCOTCHWELD 3520 B/A
05504	539	FILM KAPTON/FEP TEFLON
05505	680	LACING TAPE NYLON
05506	487	FABRIC PBI
05507	416	CORD FIBERGLASS RESIN TREATED
05508	528	FELT MICROFIBER TYPE E 4-6 LBS
05510	1,350	RUBBER SILICONE RTV 602 CLEAR
05512	84	ADHESIVE DAPCOTAC 3008 EPOXY
05513	529	FELT NOMEX/DC92-007 SILICONE COATED
05514	529	FELT NOMEX/SILICONE COATED
05515		DELETED SEE 05514
05516	1,302	RUBBER NEOPRENE C557-70
05517	363	COATING MOIST BARRIER SIM-LRSI
05518	363	COATING MOIST BARRIER SIM-HRSI
05519	1,335	RUBBER SILICONE E2024/20412038
05520	734	LUBE DRY TIOLUBE 460 MS21063
05521	661	KEL-F 81
05522	768	MOLD COMPOUND MACROLON 3000
05523	456	FABRIC GLASS/SILICONE
05524	1,405	SPONGE RUBBER NEOPRENE KOYLON
05525	253	ADHESIVE STABOND T190 NEOPRENE
05526	1,481	TILE SILICA LI0036/OVERCOATED
05527	1,481	TILE SILICA LI0050/OVERCOATED
05528	176	ADHESIVE HYSOL 4351/3469
05529		DELETED SEE 05229
05530	256	ADHESIVE TECHKIT TS118-6
05531	783	NYLON NITEX HC3-20 MONOFILAMEN
05532	1,345	RUBBER SILICONE RTV 3116
05533	1,255	POTTING COMPOUND SCOTCHCAST 250 EPOXY
05534	300	CERAMIC ALSIMAG 35 (INORGANIC)
05535	1,451	TAPE SCOTCH 74 POLYESTER/RUBBER
05536	1,292	RUBBER FLUOROSILICONE L806-80
05537	1,302	RUBBER NEOPRENE CN3
05538	397	COMPOSITE REINFORCEMENT
05539	785	PALLADIUM OXIDE (INORG)
05540	355	COATING HUMISEAL 1B31 ACRYLIC
05541	1,221	PLASTIC VALOX 310 SEO POLYESTER
05542	395	COATING Z205 SERIES
05543	696	LAMIN EPOXY/GLASS FR4
05544	1,500	TUBING SILICONE SR200 16
05546	1,304	RUBBER NEOPRENE NS6022
05547	511	FASTENER VELCRO NOMEX HAQ 12-1-200 NYLON HOOK
05548	1,472	TEFLON TFE/1% CARBON BLACK
05549	22	ADHESIVE ABLEFILM 550 EPOXY
05550	299	CEMENT FUSED SILICA INORGANIC
05551	589	INK MARKEM 7132H

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
05552	73	ADHESIVE CHOBOND 584-29 CON/EPOXY
05553	1,249	POTTING COMPOUND COX 28 EPOXY
05554	614	INSULATION FOAM ECCOFOAM FPH POLYURETHANE
05555	315	COATING 663-Z-20/C110 POLYURETHANE
05556	348	COATING EPOXY AMINE
05557	1,276	RUBBER CHOSEAL 1221 AG/FLUOROSILICONE
05558	1,276	RUBBER CHOSEAL 1217 FLUORO SILICONE/AG FILLED
05559	368	COATING PHOSPHATE (INORGANIC)
05560	184	ADHESIVE LOCTITE 306 ACRYLIC
05561	1,306	RUBBER NITRILE
05562	1,388	SEALANT GRAPHITE PUREBON P5N
05563	127	ADHESIVE EPIBOND 87399 EPOXY
05564	632	INSULATION FOAM POLYURETHANE FR6704/EC2241 4PCF
05565	1,251	POTTING COMPOUND EPOXY EC1469
05566	744	LUBE GREASE HYDROCARBON AF903
05567	342	COATING DER 332 RESIN/MXDA CAT
05568	737	LUBE FLUOROCARB MS136 TELOMER
05569	1,419	TAPE G143902 TFE/GLASS/GOLD/SILICONE ADHESIVE
05570	1,357	RUBBER SILICONE S469-40
05571	1,337	RUBBER SILICONE HARDNESS SHORE "A" 45-55
05572	1,244	POTTING COMPOUND IMPCO RC2 POLYESTER
05573	1,328	RUBBER SILICONE CHOSEAL 1215
05574	417	CORD KEVLAR/NOMEX
05575	1,436	TAPE P224 KAPTON/ACRYLIC ADHESIVE
05576	1,471	TEFLON TFE RED STRIPED
05577	309	COATING 100PWB CONFIG
05578	710	LAMIN GT100/GT420/GT10/QR43117
05580		DELETED SEE 01716
05581	346	COATING ENAMEL HS767/EPX HS768 A1
05582	198	ADHESIVE METREGRIP 303
05583	1,257	POTTING COMPOUND SCOTCHCAST EC243EPX
05584	58	ADHESIVE C15-015 A/B EPOXY
05585	766	MOLD COMPOUND EPOXY/GL/MIN 409-451
05586	1,444	TAPE SCOTCH 1245 CU WITH SILICONE ADHESIVE
05588	1,335	RUBBER SILICONE E2041 HI-DAMP
05589	1,335	RUBBER SILICONE E2038 HI-DAMP
05590	705	LAMIN EPOXY/KEVLAR CE9010/7781
05591	1,256	POTTING COMPOUND SCOTCHCAST 9 EPOXY
05592	1,251	POTTING COMPOUND EPOXY C9-4215
05593	590	INK MARKING FRS6811 BLACK
05594	1,441	TAPE POLYIMIDE X1156/SILICONE ADHESIVE
05595	1,330	RUBBER SILICONE CHOTHERM 1664
05596	1,276	RUBBER CHOSEAL 1250REI/SIL/AG
05597	1,423	TAPE GLASS A2278 ADHESIVE
05598	619	INSULATION FOAM LAST-A-FOAM POLYURETHANE FR3704
05599	1,431	TAPE MYSTIK 7100 GLASS/SILICONE ADHESIVE
05600	111	ADHESIVE ECCOBOND 56C EPOXY
05601	1,460	TAPE SCOTCHSEAL 3655 VINYL BLACK
05602	751	LUBE METAL/GLASS PS101 INORGANIC
05603		DELETED SEE 05473
05604	100	ADHESIVE EA828/VERSAMID 125/FILLED
05605	152	ADHESIVE EPOXY P460
05607	1,498	TUBING PVF RT1800/1 FLUOROELA
05608	110	ADHESIVE ECCOBOND 285/24LV EPOXY
05609	675	LACING TAPE HT-15 LOC NOMEX
05610	490	FABRIC POLYAMIDE TYPE ASI
05611	1,327	RUBBER SILICONE 5557
05612	86	ADHESIVE DELTABOND 152 WITH B4
05613	362	COATING MACUMASK 9446 EPOXY
05614	389	COATING TEFLON INFUSED
05615	421	CORE HONEYCOMB PHENOLIC/GLASS
05616	1,457	TAPE SCOTCHCAL 3651 RED
05617	565	GLASS TEMPERED(INORGANIC)
05618	1,354	RUBBER SILICONE RTV 90
05619	1,306	RUBBER NITRILE
05620	253	ADHESIVE STABOND C136 NITRILE
05621	539	FILM KEMIT 5518 POLYIMIDE/TFE/LUBRICANT
05622	1,468	TECFLUORFIL RMB1 TFE/CERAM/DYE
05623	1,301	RUBBER NEOPRENE
05624	156	ADHESIVE EPOXYLITE 6203 COATING
05625	652	INSULATION GLASS/PHENOLIC PEL05
05626	275	ADHESIVE VERSALON XR1200 POLYAMIDE
05627	762	MILK OF MAGNESIA
05628	684	LACING TAPE THERMOFLEX 1200
05629	418	CORD NOMEX 2400 DENIER
05630	418	CORD NOMEX 1200 DENIER
05631	770	MOLD COMPOUND POLYETHYLENE
05632	748	LUBE GREASE SILICONE DC971V
05633	358	COATING IRIDITE 7 INORGANIC
05634	1,504	TUBING VARGLASS H/HO NON-FRAY
05635	1,259	POTTING COMPOUND STYCAST 2762/17
05636	716	LAMIN POLYIMIDE/GLASS F174
05637	1,487	TUBING FP301 INSULTITE HST
05638	734	LUBE DRY TRANSLUBE 20204
05639	1,391	SEALANT POLYSULFIDE PRP1436
05641	569	GREASE HYDROCARBON
05642	394	COATING WATERPROOF RSI TILES
05643	1,327	RUBBER SILICONE 566/NAPTHA SOLV
05644	391	COATING UNICOAT 2081-31A EPOXY
05645		DELETED SEE 02343
05646	1,346	RUBBER SILICONE RTV 3140/1204
05647	743	LUBE GREASE ECCOTHERM TC4
05648	15	ADHESIVE ABLEBOND 150-6 EPOXY
05649	107	ADHESIVE EC2290 EPOXY
05651	396	COLODIAL SILICA SPHERES (INOR)
05652	1,400	SILICA FUSED SLIPCAST INORG
05653	587	INK EPOXY
05654	1,255	POTTING COMPOUND SCOTCHCAST 235 EPOXY
05655	690	LAMIN EPOXY/GLASS
05656	23	ADHESIVE ABLEFOAM 1 EPOXY
05657	366	COATING PC 29/29M POLYURETHANE
05658	512	FASTENER VELCRO NOMEX HAQ 12-2-200 NYLON LOOP
05659	761	MICA 495320/DFGC (INORG)
05660	1,473	TEFLON TFE/25% GLASS
05661	1,402	SODIUM SILICATE(N) INORGANIC
05662	344	COATING E42GP22/V66KP46 EPOXY
05663	300	CERAMIC ALSIMAG 771 (INORG)
05664	766	MOLD COMPOUND EPOCAST 409-608 EPOXY
05665	544	FILM MYLAR POLYLOK
05666	298	CEMENT #78 (INORG)

MSFC-HDBK-527 REV F 9999942 0006688 4

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
05668	1,306	RUBBER NITRILE
05669	1,507	VARNISH GLYPTAL RED CAT 90-2
05670	1,347	RUBBER SILICONE RTV 325
05671	1,261	POTTING COMPOUND SYLGARD 183
05672	1,244	POTTING COMPOUND BERLON E0383
05673	562	GASKET MATERIAL RUBBER SILICONE/NOMEX
05674	1,244	POTTING COMPOUND BERLON E33
05675	785	PAD ATTENUATION HFT 3/16 4.0
05676	571	HEATER BLANKET 372-4571 1-3N-4
05677	730	LUBE DRY KALGARD RA MOS2
05678	589	INK MARKEM 7254 P/K BLACK
05679	716	LAMIN POLYIMIDE/GLASS CP2252/7781
05680	1,343	RUBBER SILICONE RTV 142
05681	1,259	POTTING COMPOUND STYCAST 2651MM EPOXY
05682	668	LABEL IDENTIFICATION MYLAR ADHESIVE 853/CLEAR
05683	1,330	RUBBER SILICONE CHOTHERM 1661
05684	695	LAMIN EPOXY/GLASS EG752
05686	99	ADHESIVE EA828/DTA/AL POWDER EPOXY
05687	589	INK MARKING 1448 BLACK
05688	312	COATING 463-12-8/C-116 EPOXY
05689	1,328	RUBBER SILICONE CHOSEAL 1212
05691	1,409	SPONGE RUBBER VITON 1028
05692	1,438	TAPE P423 TFE/SILICONE
05693	1,344	RUBBER SILICONE RTV 21
05694	220	ADHESIVE POLYSULFIDE PR14600
05695	1,251	POTTING COMPOUND EPIREZ 5071/EPI841
05696	301	CERAMIC CEMENT PBX
05697	562	GASKET POLASHEET SILICONE/MONEL
05698	619	INSULATION FOAM LUNAR F20 A/B EPOXY
05699	19	ADHESIVE ABLEBOND 793-3 EPOXY
05700	86	ADHESIVE DC96-069 SILICONE
05701	1,351	RUBBER SILICONE RTV 632
05702	1,278	RUBBER COHRLASTIC R10460 SILICONE
05703	1,306	RUBBER NITRILE
05704	678	LACING TAPE NOMEX ORANGE
05705	618	INSULATION FOAM KOROPON SUPER/RTV560/HYPOLIN
05707	459	FABRIC HT-244-36 NOMEX NATURAL
05709	128	ADHESIVE EPIREZ 510
05710	786	PAPER 414 NOMEX
05711	1,336	RUBBER SILICONE GR 2
05713	564	GLASS COMPRESSION (INORGANIC)
05714	23	ADHESIVE ABLETHERM 12-1 SILICONE
05715	1,507	VARNISH INSULON 100 EPOXY
05716	395	COATING XR5133 EPOXY
05717	697	LAMIN EPOXY/GLASS K1041 POLYURETHANE COATED
05718	729	LUBE DRY INVELCO 33F
05719	732	LUBE DRY MOLYKOTE 505
05720	316	COATING 7312-A01F GRAY POLYURETHANE
05721	1,386	SEALANT COLAD 984 A/B
05723	725	LUBE DRY
05724	427	DUCT GLASS/POLYIMIDE 7781/F178
05725	1,273	RUBBER BUTYL B318-70
05726	598	INK WORNOWINK M-9-N/100 PARTS BY WEIGHT OF INK BLENDED WITH 4.9 PARTS BY WEIGHT OF CATALYST
05727	358	COATING ISONEL 31 POLYESTER
05728	1,291	RUBBER FLUOROSILICONE
05729	1,331	RUBBER SILICONE CL 2A & 2B GR 40
05731	345	COATING ENAMEL 5002 FED 595027038
05732	1,529	WIRE ELEC PTFE/GLASS FEP
05733	637	INSULATION FOAM PYRELL UNCOATED
05734	382	COATING REFSET RL4389 CRYO-INSULATION
05735	1,361	RUBBER SILICONE SM3500-41
05736	1,472	TEFLON TFE/15% GRAPHITE
05737	529	FELT TECKFELT 45-09811
05738	1,394	SEALANT SILICONE/NOMEX HT-5
05739	651	INSULATION GLASS/NYLON RF1006-HS
05740	1,357	RUBBER SILICONE S571
05741	253	ADHESIVE STABOND N125 NEOPRENE
05742	1,342	RUBBER SILICONE RTV 118
05743	59	ADHESIVE C9-42101/H3561 EPOXY
05745	108	ADHESIVE ECCOBOND 104 EPOXY
05746	1,340	RUBBER SILICONE PRP11207
05747		DELETED SEE 05218
05748	729	LUBE DRY FILM
05749	421	CORE SPIRALGRIP/A1GG220 FM1000
05750		DELETED SEE 00106
05751	328	COATING C7-23/C10-32
05752	112	ADHESIVE ECCOBOND 70C EPOXY
05753	1,329	RUBBER SILICONE CHOSEAL 1224
05754	346	COATING ENAMEL GLOSS BLACK
05755	770	MOLD COMPOUND POLYESTER
05756	762	MOLD COMPOUND ALKD 2301 GLASS
05757	346	COATING ENAMEL GREY
05758	1,261	POTTING COMPOUND SYLGARD 184
05759	1,504	TUBING VITON RT1146 HST
05760	960	PLASTIC LEXAN MR4000 SERIES
05761	701	LAMIN EPOXY/GLASS/1B31 POLYURETHANE COATED
05762	1,339	RUBBER SILICONE NICKEL FILLED ADHESIVE
05763	394	COATING X300 EPOXY
05764	378	COATING PREPARAKOAT 3055S
05765	703	LAMIN EPOXY/GRAPHITE F263
05766	374	COATING POLYURETHANE RED 21105
05767	1,309	RUBBER NORDEL EPT75
05769	592	INK PASTE BLACK 41
05770		DELETED SEE 01811
05771	1,342	RUBBER SILICONE RTV 108
05773	380	COATING PYRALENE C
05774	1,483	TUBING 4100 EPOXY POLYAMINE
05775	325	COATING ANTIREFLECTIVE INORGANIC
05776	287	BORON NITRIDE (INORG)
05777	1,354	RUBBER SILICONE RTV 955
05778	369	COATING PLYTILE R294-151B EPOXY
05779	133	ADHESIVE EPON 815/MDA EPOXY
05780	132	ADHESIVE EPON 815 EPOXY
05781	470	FABRIC NOMEX 410
05782	1,034	PLASTIC PENTON
05783	694	LAMIN EPOXY/GLASS COATED WITH CE1155
05784	336	COATING CONATHANE EN4 (DPEN6385)
05785	1,392	SEALANT PROSEAL 247A/B URETH
05786	538	FILM KAPTON GOLDIZED MMD10038

MSFC-HDBK-527 REV F ■ 9999942 0006689 6 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
05787	140	ADHESIVE EPON 828/VERSAMID 125
05788		DELETED SEE 05439
05789	743	LUBE GREASE DC4 SILICONE
05790	346	COATING ENAMEL SEMIGLOSS GRAY
05791	769	MOLD COMPOUND NORYL SE-1-GFN3 30
05792	266	ADHESIVE TYPLY 3
05793	1,362	RUBBER SILICONE SRB0607
05794	1,308	RUBBER NITRILE NCLS1
05795	1,303	RUBBER NEOPRENE NCR
05797	1,290	RUBBER FLUOROCARBON 102-7
05798	1,288	RUBBER FLUOREL 3217
05799	616	INSULATION FOAM FLUOREL G306/L3203-6
05800	1,342	RUBBER SILICONE RTV 116
05802	1,287	RUBBER FAIRPRENE 5159
05803	764	MOLD COMPOUND DAP/CARBON PROPRIETOR
05804	365	COATING NYTUFF TEFLON ANODIZED
05805	342	COATING DEPTHANE GLOSS #1 POLYURETHANE
05806	6	ADHESIVE 2223 A/B EPOXY
05807	1,325	RUBBER SILICONE 24037 CARBON/FILLED
05808	786	PANEL LEXAN 934111 EDGELIGHTED
05809	381	COATING QR43117X4-176 CAT/SIL
05810	1,273	RUBBER BUTYL 823-70
05811	1,328	RUBBER SILICONE C6-1103
05812	697	LAMIN EPOXY/GLASS FURANE 203
05813	112	ADHESIVE ECCOBOND 787 A/B EPOXY
05814	1,282	RUBBER EPR 3177
05815	1,244	POTTING COMPOUND ABLECAST 402
05816		DELETED SEE 05783
05817	59	ADHESIVE C9-4198/H2-3561
05818	1,392	SEALANT PROSEAL 727-2-3 POLYSULFIDE
05820	688	LAMIN EPOXY/ARAMID
05821	157	ADHESIVE EPOXYLITE 813-9 COATING
05822	1,451	TAPE SCOTCH 69 GLASS/SILICONE/ADHESIVE
05823	733	LUBE DRY MOLYKOTE G
05824	1,334	RUBBER SILICONE DC90-006
05825	343	COATING DURACHEM 13905 EPOXY
05826	730	LUBE DRY LUBELOK 5306
05827	635	INSULATION FOAM POLYURETHANE/FABRIC/REFSET COAT
05828	562	GASKET MATERIAL X106 NOMEX/RUBBER
05829	220	ADHESIVE POLYURETHANE C7-4247
05830	1,244	POTTING COMPOUND C9-4210/H2-3561/2775
05831	1,420	TAPE G404200/G404202TFE/AG/SILICONE ADHESIVE
05832	1,420	TAPE G404300/G404302 5 MIL TYPE A TEFLON WITH VACUUM DEPOSITED SILVER AND INCONEL WITH PERMACEL 223 SILICONE
05833	1,327	RUBBER SILICONE 92276
05834		DELETED SEE 05833
05835	1,411	STREAMER WARNING MD175-6108
05836	1,304	RUBBER NEOPRENE PRP2337
05837	1,302	RUBBER NEOPRENE C147-70
05838	665	KYNAR PLASTIC FLUORIDE
05840	1,273	RUBBER BUTYL AP2712 CL RC615
05841	1,326	RUBBER SILICONE 434
05842	1,347	RUBBER SILICONE RTV 4515
05843	765	MOLD COMPOUND EPIALL 1908
05844	250	ADHESIVE SM8103 SILICONE
05845	150	ADHESIVE EPOXY AO1503
05846	373	COATING POLYURETHANE PR1535
05847	445	FABRIC DACRON 601/SILICONE SE7501
05848	479	FABRIC NOMEX/BETA GLASS 2458N
05849	583	INK 944
05850	260	ADHESIVE THIXON 806 (AP1442)
05851	1,264	PURAFIL AL203/KMN04 INORGANIC
05852	766	MOLD COMPOUND EPOXY 403-53
05853	595	INK SERIES 39000
05854	579	HOSE TEFLON 1% CONDUCT ADDITIX
05855	1,258	POTTING COMPOUND STYCAST 1970
05856	530	FERRITE FERROXCUBE 3C8 INORGAN
05857	109	ADHESIVE ECCOBOND 276/C17
05858	456	FABRIC GLASS/SILICONE
05859	1,465	TAPE TEMP-R-TAPE K250
05860	581	INK 17
05861	1,390	SEALANT POLYSULFIDE 1221B-2
05862	16	ADHESIVE ABLEBOND 293-1
05863	1,257	POTTING COMPOUND SCOTCHCAST XR5068
05864	47	ADHESIVE ARMSTRONG X81/A EPOXY
05865	589	INK MARKEM 7907 SILK SCREEN
05866	773	MOLD COMPOUND S-8723 EPOXY
05867	1,536	YARN KELVAR 29 TYPE 964
05868	179	ADHESIVE JW7-12 ACRYLIC
05869	734	LUBE DRY TIOLUBE 450
05870	1,454	TAPE SCOTCH X1169 MYLAR RUBBER ADHESIVE
05871		DELETED SEE 05038
05872	1,324	RUBBER SILICONE 11/T12/RTV9811
05873	783	NYLON GLASS FILLED NY-029-S
05875	1,448	TAPE SCOTCH 53 POLYESTER
05876	384	COATING SEMIGLOSS ENAMEL ZN/CR04
05877	167	ADHESIVE FILM LF0400 PYRALUX
05878	1,390	SEALANT POLYSULFIDE PR1750B
05879	1,445	TAPE SCOTCH 3 ELECTRIC
05880	1,328	RUBBER SILICONE AP3004 CL 3A GR 50
05881	101	ADHESIVE EA926 EPOXY
05882	698	LAMIN EPOXY/GLASS MIB MATERIAL
05883	1,351	RUBBER SILICONE RTV 634
05884	1,363	RUBBER SILICONE TA52
05885	1,409	SPONGE RUBBER SILICONE Y3233
05886	731	LUBE DRY MOLYKOTE 106 MOS2
05887	1,496	TUBING POLYOLEFIN RT301
05888	589	INK MARKEM 8855 WHITE
05889	1,350	RUBBER SILICONE RTV 60
05890	141	ADHESIVE EPON 828/Z CURING AGENT
05891	571	HEATER BLANKET 81873/840002G
05892	314	COATING 519X303/020X324/910X357
05893	358	COATING KP420/6383
05894	314	COATING 529-001/910-037/020-004
05895	384	COATING SERMETEL TW
05896	1,448	TAPE SCOTCH 5413 KAPTON WITH SILICONE ADHESIVE
05897	405	CONNECTOR 40M MODIFIED
05898	615	INSULATION FOAM ECCOFOAM FPH/FC721 COATED
05899	590	INK MARKING K36 BLACK

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
05900	683	LACING TAPE TFE/RUBBER H 231H
05901	588	INK L-O-N SERIES MARKING
05902	586	INK DEUTSCH DPS I140-01 MARKNG
05903	587	INK FRS MARKING 7224
05904	1,372	RUBBER VITON 9009-90
05905	1,371	RUBBER VITON 9009-75
05906	1,370	RUBBER VITON 19357
05908	327	COATING BLACK ENAMEL/ZNCRO4
05909	1,536	XIRCONIA ZRO2 (INORG)
05910	783	NYLON 6/6 30% GLASS RF-1006
05911	1,466	TAPE THERMOSEAL TFE TEFLON S12
05912	115	ADHESIVE ECCOSIL W191C11/S11
05913	1,295	RUBBER KALREZ 1050
05914	683	LACING TAPE TEMP-LACE H/276H
05915	104	ADHESIVE EA9421
05916	447	FABRIC DF513/DF202 SILICONE
05917	1,303	RUBBER NEOPRENE E
05918	1,389	SEALANT NEOPRENE DAPCO 2030
05919	356	COATING HUMISEAL 2A64A/B POLYURETHANE
05920	133	ADHESIVE EPON 815/RF61/GL FT102
05921	653	INSULATION MICA BONDED GLASS INORG
05922		DELETED SEE 06067
05923	416	CORD KEVLAR 1600 KDE 29 ARAMID
05924	1,342	RUBBER SILICONE RTV 112
05925	683	LACING TAPE TFE 2560
05926	1,488	TUBING GLASS/SILICONE K26-2-305
05927	353	COATING GAGEKOTE 5
05928	254	ADHESIVE STYCAST 2741/C15
05929	1,252	POTTING COMPOUND FM1132 PHENOLIC
05930	396	COATING ZINC RICH T1 C1 INORGANIC
05931	1,416	TAPE E125 TEFLON
05932	319	COATING 850-204 TFE GREEN
05933	336	COATING CONAPOXY 1122
05934	454	FABRIC GLASS FIBER VARNISHED
05935	1,253	POTTING COMPOUND PR1547 BLACK POLYURETHANE
05936	343	COATING DK403 EPOXY DRY POWDER
05937	1,445	TAPE SCOTCH 3082 TEFLON
05938	766	MOLD COMPOUND EPOXY 2748
05939	625	INSULATION FOAM PDL4034-2.5S/RL4389/TAPE
05940	563	GASKET SILICONE 7241/KEVLAR K120
05941	466	FABRIC M380-3 FIBERGLASS/TFE
05942	149	ADHESIVE EPOXY 500
05943	108	ADHESIVE ECCOBOND 104/ALUMINA
05944	320	COATING 851-245 TOPCOAT/850-204 PRIMER
05945	227	ADHESIVE R393
05946	538	FILM KAPTON H
05948	249	ADHESIVE SILICONE G661
05949	374	COATING POLYURETHANE PR1654
05950	489	FABRIC PBI S-164 FX RASCHELNET
05951	363	COATING MXP130
05952	751	LUBE NASA PS101/C800 INORGANIC
05953	372	COATING POLYURETHANE ORANGE INTL 12197
05954	1,399	SILICA DYNASIL 5000 FUSED INORGANIC
05955	1,420	TAPE G401902 FEP WITH 467 ACRYLIC ADHESIVE
05956	347	COATING EPON 1001/VERSAMID 115
05957	185	ADHESIVE LOCTITE 416 CYANOACRYLIC
05958	1,360	RUBBER SILICONE SE7600
05959	1,326	RUBBER SILICONE 555
05960	1,503	TUBING TYGON R3603
05961	341	COATING DC Z6070 SILANE
05962	395	COATING X75207-66 EPOXY/ENAMEL
05963	83	ADHESIVE CYCLEWELD 55-9
05964	174	ADHESIVE GRIGG G570
05965	288	BRAKE MATERIAL 4813
05966	1,323	RUBBER SILASTIC RTV 731
05967	278	ADHESIVE XFBC543
05968	169	ADHESIVE FOAM FM37 MODIFIED EPOXY
05969		DELETED SEE 05310
05970	24	ADHESIVE ADX3103.1 EPOXY
05971		DELETED SEE 06587
05972	392	COATING URAMET 4-1W-12 #100 GRIT
05973	559	FLUOROLOY D
05974	1,494	TUBING POLYOLEFIN DUAL WALL HST
05975	281	ARMALON TG 4102
05976		DELETED SEE 03449
05977	765	MOLD COMPOUND EPIALL 1288BX
05979	683	LACING TAPE STUR-30
05980	1,279	RUBBER CONSIL 2 SILICONE/AG FILLED
05981	257	ADHESIVE THERMASIL 1 MODIFIED
05983	317	COATING 822-327 POLYURETHANE FLAT GRAY
05985	713	LAMIN OVERCOAT WITH 1B31/FC721
05986	382	COATING RESIN LIQUID TYPE MC6
05987	677	LACING TAPE NOMEX
05990	567	GRAPHITAR GRADE 14
05991	1,529	WIRE ELEC PT COND/MGO INS/MET
05992	350	COATING EPOXY WHITE 37875
05993	348	COATING EPOXY GRAY 36118
05994	385	COATING SILICONE (INORGANIC)
05995	1,454	TAPE SCOTCH X1170
05996	588	INK K486 HOT STAMP BLUE-BLACK
05997	1,294	RUBBER KALREZ 1045
05998	299	CERAMIC AB312 FABRIC/POLYETHYLENE
05999	655	INSULATION SAFFIL ALUMINA HT MAT
06001	460	FABRIC HT-46-XX ARAMID WOVEN
06002	387	COATING SILICONE XRTV6343
06003	784	NYLON/15% GLASS
06004	352	COATING FLUORAD FC721
06006	718	LAMIN TEFLON TFE/GLASS
06007	1,449	TAPE SCOTCH 5451
06008	1,051	PLASTIC PLEXIGLASS GM2064 GRAY
06009	156	ADHESIVE EPOXYLITE 5403 EPOXY
06010	636	INSULATION FOAM PYRELL LS645CZ
06011	1,423	TAPE G550 FIBERGLASS/ACRYLIC
06012		DELETED SEE 06067
06013	1,421	TAPE G40700 KAPTON/GOLD ADHESIVE
06014	258	ADHESIVE THERMASIL T2/CS
06015	112	ADHESIVE ECCOBOND 66C EPOXY
06016	1,328	RUBBER SILICONE BTR
06017	1,507	VARNISH IMPREGNATING SR224 SILICONE
06018	691	LAMIN EPOXY/GLASS 500

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006691 4

MATCD	PAGE	DESIGNATION
06019	586	INK COLITHO 0691-19003/JCP E20
06020	789	PAPER JCP K-20
06021	789	PAPER JCP K-10
06022	1,481	TONER HUNT UNIVERSAL 36
06023	1,481	TONER XEROX 6500
06024	503	FABULON
06025	286	BOARD DRAWING 4-PLY
06026	1,481	TISSUE DRY MOUNT MT5
06027	592	INK PENTEL PEN S360 ALL TYPES
06028	1,463	TAPE TEMP-R-GLASS A2008
06029	320	COATING 856-204/855-225/850-204
06030	320	COATING 851-204/851-224 TFE
06031	1,407	SPONGE RUBBER SILICONE ADHESIVE PS
06032	389	COATING TEMPILAQ GR800
06033	669	LABEL IDENTIFICATION TEMPILABEL BE2XXF
06034	320	COATING 851-225 BLK/850-201
06035	1	ABLATOR SLA 561
06037	1,469	TEFLON PFA S160 #10299
06039	625	INSULATION FOAM PDL4034-2.5S/ENSHROUDED IN METAL FOIL
06040	703	LAMIN EPOXY/GRAPHITE GY70/E42
06041	1,394	SEALANT SYNKOLOID VINYL SPACKL
06042	1,275	RUBBER CHOSEAL 1214 WITH AG/SILICONE
06043	311	COATING 453-3-33 EPOXY
06044	327	COATING C12546 EPOXY
06045	315	COATING 59-000 SERIES EPOXY
06046	9	ADHESIVE 453/EC3917 EPOXY FILM
06047	554	FILM TFE LPN123 GRAPHITE FILL
06048		DELETED SEE 62574
06049	154	ADHESIVE EPOXY RW1290-82
06050	319	COATING 851-204 TEFLON PRIMER
06051	1,426	TAPE LACING S199 POLYIMIDE
06052	536	FILM G145100 .5 MIL KAPTON .9 OZ PER SQUARE YARD NOMEX SCRIM
06053	1,467	TAPE X389-25-1 BETA GL TEFLON
06054	348	COATING EPOXY E81552 ELEC INSUL
06055	302	CERAMIC MACOR (INORGANIC)
06056	769	MOLD COMPOUND NYLATRON MOS2 FILLED
06057	601	INSULATION BLANKET MC364-0011
06058	363	COATING METAL BLUEING (INORGANIC)
06059	1,451	TAPE SCOTCH 64 TFE/GLASS/SILICONE
06060	268	ADHESIVE UNISET A316-4 EPOXY
06061	679	LACING TAPE NOMEX/P/N 950H0T16
06062	1,486	TUBING FIBERGLASS S1600-H
06063	362	COATING LATEX FRL3 FLAME RETARDANT
06064	257	ADHESIVE THERMAL CONDUCT SILICONE
06066	651	INSULATION GLASS WIRE IMPRG SYS T/C
06067	1,273	RUBBER BUTYL R/S 201-6
06068	3	ACRYLIC SHEET SI60948 STRETCH
06069	322	COATING A4094 SILICONE
06070	656	INSULATION SIC IMR SI02/GLAZE
06071	300	CERAMIC AD995 ALUMINA (INORG)
06072	338	COATING CTL15/C15 CAT EPOXY BLACK
06073	364	COATING NA7509-V73/NA7486-V66 PLU
06074	503	FABRIC X-389-7 BETA/GLASS/TFE
06076	109	ADHESIVE ECCOBOND 24
06077	338	COATING D4D THERMAL CONTROL ALUMINUM/SILICONE
06081	256	ADHESIVE SYS-SILICA (INORGANIC)
06082	233	ADHESIVE SAUEREISEN #8 INORGANIC
06083	711	LAMIN KEVLAR 49/LY8061 EPOXY
06084	618	INSULATION FOAM KUA100
06085	1,327	RUBBER SILICONE 77C 12640
06086	1,511	VESPEL SP22 POLYIMIDE/40% GRAPHITE
06087	1,483	TUBING BEN-HAR ST
06088	559	FLUOROGREEN E-600 TFE/GLASS
06089	455	FABRIC GLASS/PTFE COATED VM3033
06090	1,356	RUBBER SILICONE S383-70
06091	1,256	POTTING COMPOUND SCOTCHCAST 8
06092	1,450	TAPE SCOTCH 63
06093	339	COATING DC 1107 INSUL FLUID
06094	1,308	RUBBER NITRILE N506-65
06095	1,440	TAPE POLYIMIDE T966
06096	1,440	TAPE POLYIMIDE AU/AL PS ADHESIVE
06097	529	FELT REFRASIL B100 SILICA
06098	344	COATING EC3901
06099	231	ADHESIVE RMI380 EPOXY
06100	474	FABRIC NOMEX K-GUARD CLR#21302
06101	1,335	RUBBER SILICONE E2053 HI DAMP
06103	1,528	WIRE ELEC MAGNET POLYESTER-IMIDE OR POLYESTER-AMIDE-IMIDE CL 180 TYPE H
06104	374	COATING POLYURETHANE PR420
06105	373	COATING POLYURETHANE PR1506
06106	373	COATING POLYURETHANE PR1564
06107	1,489	TUBING INDULITE PS1015 TFE
06108	1,354	RUBBER SILICONE RTV 881
06109	1,253	POTTING COMPOUND POLYURETHANE PRP1538
06110	747	LUBE GREASE SILICONE DC5
06111	1,358	RUBBER SILICONE S6535
06112	1,269	ROPE SILICA SS1404 (INORGANIC)
06113	755	LUBE OIL SYNTHETIC (DIESTER)
06114	731	LUBE DRY LUBRIBOND HT MOS2/ST
06115	734	LUBE DRY SPRAYKOTE MOS2/SILICONE
06116	400	COMPOUND HEAT SINK THERMAL 120
06117	603	INSULATION FLEX MIN-K TY5 HT
06118	1,435	TAPE P211 GLASS/SILICONE ADHESIVE
06119	591	INK MARKING RADIOGRAPH 580005
06120	1,252	POTTING COMPOUND EPOXYLITE 210/C321
06121	457	FABRIC GLASS/TFE COATED M381-10
06122	1,444	TAPE SCOTCH 1170 ALUMINUM FOIL CONDUCTIVE ACRYLIC ADHESIVE
06123	1,446	TAPE SCOTCH 433 ALUMINUM FOIL WITH SILICONE ADHESIVE
06124	1,502	TUBING THERMOFIT S1009 EPOXY
06125	326	COATING BISPHENOL A EPOXY FLDIZE
06127		DELETED SEE 05473
06128	350	COATING EPOXY U122W
06129	152	ADHESIVE EPOXY PATCH KIT 1C
06130	254	ADHESIVE STYCAST 3020
06131	17	ADHESIVE ABLEBOND 369-3 CONDUCTIVE
06132	100	ADHESIVE EA901/B1

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006692 6

MATCD	PAGE	DESIGNATION
06133	1,435	TAPE P212 GLASS/SILICONE ADHESIVE
06134	2	ABSORBER RF IRON/EPOXY EMA 719
06135	158	ADHESIVE EPOXYLITE CF8628 EP
06136	130	ADHESIVE EPOCAST 290 EPOXY
06138	740	LUBE GREASE BRAYCOTE 3L-38ZN
06139	1,250	POTTING COMPOUND COX 4021/4036
06140	773	MOLD COMPOUND TPX METHYLPENTENE
06141	1,420	TAPE G401900 5 MIL TYPE A TEFLON WITH VAC DEPOSITED SILVER AND INCONEL WITH 966 ACRYLIC ADHESIVE
06142	302	CERAMIC LITHAFRAX (INORGANIC)
06143	112	ADHESIVE ECCOBOND SOLDER 57C
06144	1,338	RUBBER SILICONE NE6016
06145	1,336	RUBBER SILICONE FUEL/OIL RESIS
06146	732	LUBE DRY MOLYKOTE 44
06147	1,338	RUBBER SILICONE NE6071/6071
06148	1,363	RUBBER SILICONE TH1243/TH1166
06149	1,363	RUBBER SILICONE TH1217
06150	1,363	RUBBER SILICONE TH1242/TH1165
06151	1,318	RUBBER SILASTIC 35U
06152	51	ADHESIVE BONDMASTER 81-0590
06153	434	FABRIC 5035/8362 BETA/SILICONE
06154	732	LUBE DRY MOLYKOTE 321R
06155	1,338	RUBBER SILICONE NE687B/5687
06156	1,341	RUBBER SILICONE REDAR S59-808
06157	564	GASKET SILICONE/AL RFI 04-0102
06158	1,361	RUBBER SILICONE SM3500-55
06159	1,308	RUBBER NITRILE N756-75
06160	343	COATING E2359A/B EPOXY
06161	89	ADHESIVE DEVCON 2-TON EPOXY WHITE
06162	556	FILTER MICROFIBER GLASS/EPOXY
06163	165	ADHESIVE FILM FM123-2LVC EPOXY
06164	115	ADHESIVE ECCOSORB MF-S124
06165	111	ADHESIVE ECCOBOND 59C/C59C
06166	1,464	TAPE TEMP-R-TAPE C
06167	248	ADHESIVE SILGRIP SR573 SILICONE
06168	1,536	YARN GLASS/TFE SF-542
06170	153	ADHESIVE EPOXY PATCH KIT 608
06171	153	ADHESIVE EPOXY PATCH KIT 56C WHITE
06172	733	LUBE DRY MOLYKOTE Z MOS2 INORGANIC
06173	334	COATING CHEMGLAZE Z306
06174	1,254	POTTING COMPOUND REZOLIN 185N POLYURETHANE
06175	181	ADHESIVE LEFKOWELD 109/LM52 EPOXY
06176	694	LAMIN EPOXY/GLASS CORDOPREG E293
06177	330	COATING CHEMGLAZE 9924 A/B
06178	66	ADHESIVE CERAMIC 503 INORGANIC
06179	746	LUBE GREASE KRYTOX 283AB
06180	154	ADHESIVE EPOXY R82038/HD3475
06181	355	COATING HUMISEAL 1A33 POLYURETHANE
06182	1,356	RUBBER SILICONE RUBBERCRAFT 59
06183	279	ADHESIVE Z50 ACRYLIC
06184	1,389	SEALANT PLENUM SHELL CVR POLYURETHANE
06185	387	COATING SLIP RESISTANT POLYURETHANE
06186	1,426	TAPE KAPTON/SILICONE K350 PS
06187	1,424	TAPE GV FIBERGLASS/SILICONE/ADHESIVE
06188	1,445	TAPE SCOTCH 361 GLASS/SILICONE/ADHESIVE
06189	321	COATING 959-203 TFE BLACK
06190	141	ADHESIVE EPON 828/VERSAMID 140
06191	1,341	RUBBER SILICONE RTV 106
06192	1,353	RUBBER SILICONE RTV 8111/C989
06193	1,307	RUBBER NITRILE 972
06194	695	LAMIN EPOXY/GLASS E760A/7581/D6090
06195	1,403	SOUND INSUL KNB-5LR BLACK PVC
06196	769	MOLD COMPOUND NORYL EN-265
06197	660	KEL-F 800 MEK/SPRAY
06198	1,307	RUBBER NITRILE FUEL RESISTANT
06199	742	LUBE GREASE DC2 SILICONE
06200	1,273	RUBBER BUTYL B59L-80
06201	729	LUBE DRY EVERLUBE 823
06202	301	CERAMIC DUROCK 17 OR 33
06203	299	CERAMIC 5656 (INORG)
06204	219	ADHESIVE POLYAMIDE V40
06205	202	ADHESIVE MPC52 A/B EPOXY
06206	368	COATING PLASMA CHROMIC OXIDE INORGANIC
06207	355	COATING HI EMITTANCE/WEAR R INORGANIC
06208	1,339	RUBBER SILICONE NOC
06210	743	LUBE GREASE DC970V SILICONE
06211		DELETED SEE 06164
06212	300	CERAMIC BRAID SLEEVING SF2600
06213	503	FABRIC/TAPE 581 QUARTZ (INORGANIC)
06214	333	COATING CHEMGLAZE Z202 POLYURETHANE
06215	590	INK MARKING FRSI SILICONE
06217	772	MOLD COMPOUND RYTON R-4
06218	1,440	TAPE POLYIMIDE PS ADHES
06221	496	FABRIC SILICONE/CR/PTFE V3037
06222	438	FABRIC BETA SUPER 4484/TFE COATED
06223	1,463	TAPE TEFLON/ACRYLIC 3596 PS
06224	2	ABSORBER RF IRON/EPOXY
06225	1,535	WIRE ELECTRIC FIBERGLASS
06226	1,491	TUBING KYNAR RT1150 CONVOLUTED
06227	470	FABRIC NOMEX 7878 G650
06228	1,477	THREAD NOMEX 45/3 ROYAL BLUE
06229	489	FABRIC PELLON FR 954
06230	22	ADHESIVE ABLEFILM 551 EPOXY
06231	153	ADHESIVE EPOXY PATCH KIT 9340
06232	1,517	WEBBING NOMEX
06233	315	COATING 643-1-1 POLYURETHANE
06234	1,504	TUBING VARGLASS 81600H
06235	459	FABRIC HT-16-45 NOMEX
06236	332	COATING CHEMGLAZE II A276
06237	1,356	RUBBER SILICONE RTV SWS951
06238	722	LINER DURALINER NYLON/TFE
06239	722	LINER FAFTEX NOMEX/TEFLON
06240	563	GASKET RFI 01-0504 FERREX/SILI
06241	1,444	TAPE SCOTCH 118 COPPER WITH ACRYLIC ADHESIVE
06243	1,444	TAPE SCOTCH 1267 AL/ACRYLIC/ADHESIVE
06244	675	LACING TAPE HKK KEVLAR 49
06245	1,490	TUBING KEVLAR 49
06246	384	COATING S954-207 TEFLON
06247	733	LUBE DRY MOS2/SILICATE

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006693 8 ■

MATCD	PAGE	DESIGNATION
06248	400	COMPOUND HEAT TRANSFER G642 SILICONE
06249	1,452	TAPE SCOTCH 850 POLYESTER/ACRYLIC ADHESIVE
06250	1,539	ZIPPER NOMEX/BRASS
06252	428	DUCT SILICONE/HT6 NOMEX
06253	417	CORD KRT-300 ARAMID
06254	1,515	WEBBING ELASTIC 1707
06255	532	FILM ACLAR 33C ECTFE
06256	1,323	RUBBER SILICONE 0117 DACRON REINFORCED
06257	1,335	RUBBER SILICONE E2022A HI-DAMP
06258	1,325	RUBBER SILICONE 30 SHORE
06259	770	MOLD COMPOUND PLENCO 1532 POLYESTER
06260	771	MOLD COMPOUND POLYURETHANE NC101
06261	389	COATING TECFLUOROCOTE X4 TEFLON
06262	1,348	RUBBER SILICONE RTV 511/577
06263	707	LAMIN EPOXY/PHENOLIC
06264	1,475	THREAD BETA GLASMO TEE
06265	747	LUBE GREASE RYKON PREMIUM 2EP
06266	1,480	TILE REPAIR TPS1/2/7/21/22
06267	1,481	TILE REPAIR TPS5 (INORG)
06268	1,480	TILE REPAIR TPS11 (INORG)
06269	1,253	POTTING COMPOUND PR1578 POLYURETHANE
06270	123	ADHESIVE EPIBOND 115 EPOXY
06271	454	FABRIC GAP FILLER
06272	959	PLASTIC LEXAN F60061 POLYCARBONATE
06273	272	ADHESIVE URALANE 5738 A/B POLYURETHANE
06274	1,340	RUBBER SILICONE PRP11307
06276	1,291	RUBBER FLUOROSILICONE 67XX
06277	641	INSULATION FOAM SCOTTFELT 3-900 FR POLYURETHANE
06278	362	COATING MASKANT 204-2 EPOXY BASE
06279	1,419	TAPE G148020 AL/POLY/NOMEX/ADHESIVE
06280	1,422	TAPE G409360 THICK BLACK FILM WITH .5 MIL KAPTON AND 966 ACRYLIC ADHESIVE
06281	136	ADHESIVE EPON 828/C906
06282	37	ADHESIVE ARALDITE 6005/906
06283	1,291	RUBBER FLUOROSILICONE 9-6500
06284		DELETED SEE 02921
06285	455	FABRIC GLASS/ALUMINUM/SILICONE SRGA2218
06286	1,339	RUBBER SILICONE O-RINGS
06287	320	COATING 851-224 GREEN/850-204 GREEN
06288		DELETED SEE 05843
06289	316	COATING 7X983 SILICONE 3709-A13
06290	313	COATING 463-4-4 PRIMER EPOXY
06291	1,285	RUBBER EPR NCLS1
06292	652	INSULATION KAOWOOL BULK A (INORG)
06293	477	FABRIC NOMEX TWILL POLYI
06294	448	FABRIC DURETTE 400-11 NOMEX
06295	725	LUBE CPD GRAPHITE/PETROLATUM
06296	704	LAMIN EPOXY/GRAPHITE HMFB3-714H
06297	738	LUBE GREASE AMDEX 2EP
06298	515	FASTENER VELCRO NYLON HOOK 2 INCH
06299	1,394	SEALANT SILICONE/FEP TEFLON
06300	379	COATING PRIMER VINYL BUTYRAL
06302	344	COATING E318315H FUSE EPOXY
06303	1,291	RUBBER FLUOROSILICONE 9-5400
06304	397	COMPOSITE EPOXY FIBERGLS A8514
06305	359	COATING KRYLON 1501 GLOSSY WHITE
06306	597	INK WARNOWINK M-9-N WITH DEPTHANE GLOSS NO. 1 OVERCOAT
06307		DELETED SEE 05805
06308	1,242	POLYCARBONATE AMBER 1663
06309	690	LAMIN EPOXY/GLASS
06310	756	LUBE SPERMAFOL 5200
06311		DELETED SEE 63491
06312	1,480	TILE HRSI WITH CC1 AMES COATING
06313	676	LACING TAPE HT-30 LOC B ORANGE
06314	401	COMPOUND PQ HEAT SINK
06315	385	COATING SILCARB/POLYETHYLENE
06316	1,517	WEBBING MURDOCK X854 POLYESTER
06317	1,483	TUBING ACRYLIC RIGID
06318	1,417	TAPE FES51 ALUMINUM GLASS WITH SILICONE ADHESIVE
06319	452	FABRIC FIBERGLASS/VITON 5707
06320		DELETED SEE 00385
06321	1,453	TAPE SCOTCH 853 POLYESTER
06322	737	LUBE EXT PRESS PETROLEUM BASE
06323	548	FILM POLAROID 3000 LAND TY 107
06324	1,388	SEALANT FRAYCHECK
06325	108	ADHESIVE EC847 NITRILE BASED
06326	1,444	TAPE SCOTCH 27 GLASS/RUBBER/ADHESIVE
06327	1,446	TAPE SCOTCH 428 ALUMINUM FOIL/RUBBER ADHESIVE
06328	256	ADHESIVE SYLGARD 187
06329	1,257	POTTING COMPOUND SCOTCHCAST XR5001
06330	453	FABRIC FLUOREL/GLASS RL3489
06331	249	ADHESIVE SILICONE BLK GL FIL
06332	115	ADHESIVE ECCOSORB VHP
06333	115	ADHESIVE ECCOSORB RF/HT99
06334	651	INSULATION GLASS FAB/AL FOIL 104
06335	545	FILM NM50-48 KAPTON/AL/ORGANIC COATED
06336	545	FILM NM50-67 KAPTON AL/ORGANIC COATED
06337	321	COATING 958-203 TEFLON
06338	324	COATING AEROSEAL CERAMIC (INORG)
06339	452	FABRIC FIBERGLASS/SILICONE 03080
06340	587	INK EPOXY BASE BLK BPS19-00-1
06341	14	ADHESIVE A5900 PHENOLIC THERMOSET
06342	744	LUBE GREASE KRYTOX 240AB
06343	70	ADHESIVE CHEMLOK 250
06344	352	COATING FUSECOTE REP35212-50
06346	1	ABLATOR 5026-39M
06347	1	ABLATOR 5026-39H/C-G
06348	131	ADHESIVE EPOCAST 87005 A/B-60
06350	1,349	RUBBER SILICONE RTV 560/FILLED INCR3
06351	368	COATING PLASTIDIP 9560T12
06352	1,274	RUBBER CHLOROPRENE C873-70
06353	454	FABRIC GLASS SILICONE SMC1050
06354	183	ADHESIVE LOCTITE 222-41
06355	184	ADHESIVE LOCTITE 222/GR-T PRIMER
06356	146	ADHESIVE EPOTEK H70E EPOXY
06357	458	FABRIC HT-10-41 NOMEX
06358		DELETED SEE 05630
06359	536	FILM G099700 VAC DEPOSITED ALUMINUM .5 MIL KAPTON STYLE 108 GLASS FABRIC WITH 3P ADHESIVE

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
06360	536	FILM G127200 VAC DEPOSITED ALUMINUM .5 KAPTON STYLE 112 GLASS FABRIC WITH 3P ADHESIVE
06361	487	FABRIC PBI 73300-250 FX BRAID
06362	473	FABRIC NOMEX COATED WITH SCOTCHGARD FC4101
06363	1,496	TUBING POLYOLEFIN RT102 HST
06364	1,350	RUBBER SILICONE RTV 602/GL-FR
06365	249	ADHESIVE SILICONE DA4
06366	338	COATING CTL/C15 EPOXY WHITE 27875
06367	698	LAMIN EPOXY/GLASS RADP70057
06368	384	COATING SEALER POLYURETHANE/EPOXY
06369	594	INK S66-17 SATURN YELLOW
06370	594	INK S66-13 ROCKET RED
06371	594	INK S66-16 ARC YELLOW
06372	594	INK S66-18 SIGNAL GREEN
06373	1,356	RUBBER SILICONE S455-70
06374	1,459	TAPE SCOTCHLITE 7610 VINYL P/S
06375	498	FABRIC SRGA 0213 ALUM/GLAS/SIL
06376	653	INSULATION MATERIAL 550-02 QUARTZ FIBER
06377	555	FILM VINYL 3650G INK COATED P/S
06378	1,508	VESPEL KS105
06379	454	FABRIC GLASS PLASTIC COATED
06380	434	FABRIC 7878 FIRE/WATER PROOF
06381	1,395	SEALANT TORR EPOXY 953-001
06382	367	COATING PC18/18M POLYURETHANE
06383	1,492	TUBING MYLAR HEAT SHRINK
06384	1,521	WEBBING PBI FRL-S169 FX
06385	1,361	RUBBER SILICONE SMC1050
06386	339	COATING DAPCOTAC 3300TH ADHESIVE
06387	424	CUSHION SEAT CREW WITH PASSENGER
06388	645	INSULATION FOAM TEMPERFOAM T47
06389	645	INSULATION FOAM TEMPERFOAM T41
06390	1,456	TAPE SCOTCHCAL 3623 VINYL ORANGE
06391	1,457	TAPE SCOTCHCAL 3652 VINYL YELLOW
06392	1,457	TAPE SCOTCHCAL 3627 VINYL GREEN
06394	1,457	TAPE SCOTCHCAL 3658 VINYL GRAY
06395	1,325	RUBBER SILICONE 159
06396	555	FILM VINYL COTTON TEXLE BACKED
06397	288	BRAKE MATERIAL S1698-5
06398	1,458	TAPE SCOTCHCAL 5690 VINYL
06399	368	COATING PHENOLIC P-5 PRIMER
06400	260	ADHESIVE THIXON 807 (AP1559) NEOPRENE
06401	1,261	POTTING COMPOUND SYLGARD 170
06402	1,480	TILE REPAIR TPS12/16 (INORG)
06403	1,481	TILE REPAIR TPS29 (INORG)
06404	492	FABRIC POLYESTER/PVS L-109 KUP
06405	367	COATING PC210 FIRE RETARDANT
06406	1,438	TAPE P50 COTTON WITH RUBBER ADHESIVE
06407	386	COATING SILICONE RED VHT SP109
06409	1,275	RUBBER CHLOROPRENE NOC
06410	140	ADHESIVE EPON 828/VERSAMID 120
06411	279	ADHESIVE XR5135 EPOXY
06412	664	KYNAR MELTABLE PIGMENTED BLUE
06413	665	KYNAR MELTABLE PIGMENTED RED
06414	665	KYNAR MELTABLE PIGMENTED YELLOW
06415	1,522	WEBBING STRAP NYLON/FC4101
06416	225	ADHESIVE PROSEAL 840 EPOXY
06417	958	PLASTIC LEXAN 9604-71063 POLYCARBONATE
06418	1,261	POTTING COMPOUND STYCAST 3050/C9
06419	527	FELT BETA GLASS C3-21-109
06420	291	CABLE CRES LUBRICATED
06421	485	FABRIC NYLON/VINYL RED 1024
06422	652	INSULATION GLASS/RUBBER SIL-PAD 400
06423	751	LUBE OIL DC510 SILICONE
06424	43	ADHESIVE ARMSTRONG A875 NITRILE RUBBER
06425	744	LUBE GREASE KRYTOX 21
06426	387	COATING SOLITHANE 113/300
06427	788	PAPER FREEZER WRAP POLYETH COATED
06428	232	ADHESIVE RUBBER SSH/SS1 SILICONE
06429	1,404	SPONGE RUBBER CELLULOSE
06430	362	COATING LATEX VINYL WT102
06431	710	LAMIN GILLFLOOR 5007A BALSA/GLASS
06432	1,412	TAPE AL/KAPTON/ORGANIC COATED
06433	502	FABRIC VD0001 DACRON/VITON
06434	1,508	VARNISH SR80 SILICONE
06435	399	COMPOUND ANTI-ICING DMSO/H20/PECTIN
06436	1,421	TAPE G406550 5 MIL TEFLON WITH 966 ACRYLIC ADHESIVE
06437	323	COATING ACRYLIC E28A
06438	592	INK PHENOL 82L22G1 BLACK
06439	340	COATING DC 1205
06440	1,424	TAPE HI/D 603A KAPTON/ACRYLIC
06441	1,255	POTTING COMPOUND SCOTCHCAST 10 EPOXY
06442	253	ADHESIVE STYCAST 2662/C14
06443	219	ADHESIVE POLYESTER ETC1
06444	151	ADHESIVE EPOXY M688
06446	787	PAPER ERZ POLYETH/FC4101 COATED
06447	1,433	TAPE NM53-57 KAPTON/AL ORGANIC COATED
06448	545	FILM NM54-15 KAPTON AL/ORGANIC COATED
06449	1,422	TAPE G411520 2 MIL$RÍ KAPTON VACUUM DEPOSITED ALUMINUM WITH ACRYLIC OVERCOAT
06450	417	CORD KEVLAR 29 B/B 16X15
06451	1,259	POTTING COMPOUND STYCAST 2850FT/C11
06452	102	ADHESIVE EA9307 EPOXY
06454	1,484	TUBING EVA ETHYLENE VINYL
06455	514	FASTENER VELCRO NYLON HAQ 12-2-100 LOOP
06456	1,451	TAPE SCOTCH 666 PVC ACRYLIC ADHESVIE
06457	1,507	VARNISH INTUMESCENT R66 FR
06458	613	INSULATION FOAM DENSITE 2 POLYESTER URETHANE 5
06459	614	INSULATION FOAM DENSITE EN-3 POLYETHER
06460	353	COATING G650 ER WHITE
06461	324	COATING ALKYD GLOSS ENAMEL YELLOW
06462	108	ADHESIVE EC4500 CHLORINATED ELAST
06463	249	ADHESIVE SILICONE 9-5939-5
06464	601	INSULATION BLANKET SILICONE/S-GLASS/Q-FELT
06465	1,476	THREAD NO B8 SIZING 636
06466	302	CERAMIC NEXTEL XC-568 F12 INOR
06467	1,334	RUBBER SILICONE DC93-076
06469		DELETED SEE 05251
06470	1,242	PLATE ID TEMPILABLE 8D-XXX/XXX
06471	1,425	TAPE KAPTON/NYLON ACRYLIC KN80

MSFC-HDBK-527 REV F 9999942 0006695 1

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
06472	1,257	POTTING COMPOUND SIL PTK 16000-002
06473	602	INSULATION FIBERFRAX 970A CERAMIC
06474	601	INSULATION CERACHROME CERAMIC INORGANIC
06475	702	LAMIN EPOXY/GRAPHITE
06476	475	FABRIC NOMEX RED 5-502 FP/WP
06477	569	GREASE ELECTROMOLY 32 POLYGLY
06478		DELETED SEE 05824
06479	1,429	TAPE MYLAR 444 FILM ACRYLIC ADHESIVE
06480	387	COATING SILICONE WHITE VHT SP101
06481	1,422	TAPE G407910 VACUUM DEPOSITED GOLD 1 MIL KAPTON WITH SILICONE ADHESIVE
06482	150	ADHESIVE EPOXY CDS64
06483	766	MOLD COMPOUND EPOXY/GLASS FILLED
06484	1,291	RUBBER FLUOROSILICONE 16438-1
06485	1,284	RUBBER EPR ER-WR-EPDM
06486	595	INK SHARPIE 3000
06487	360	COATING LACQUER NO.2 OSC877
06488	179	ADHESIVE K230 B/A
06489	1,345	RUBBER SILICONE RTV 3112/CATALYST F
06490	1,293	RUBBER FLUOROSILICONE MS55
06491	117	ADHESIVE ELASTOMERIC PROPRIETARY
06493	1,295	RUBBER KALREZ 1058
06494	1,485	TUBING FEP TEFLON
06495	1,353	RUBBER SILICONE RTV 8112 C9858
06496	664	KRATON 2701 MANIFOLD FITTING
06497	792	PELLETHANE 2103 POLYETHER TUBE
06498	596	INK SUPER 67 SIGNAL GREEN
06499	596	INK SUPER 67 SATURN YELLOW
06500	596	INK SUPER 67 ARC YELLOW
06501	596	INK SUPER 67 ROCKET RED
06503	536	FILM G412020 KAPTON/ALUMINUM/ORGANIC COATED
06504	1,423	TAPE G411970 ALUMINUM/KAPTON/ADHESIVE
06505	1,484	TUBING ESTANE
06506	1,500	TUBING SOLPRENE 416
06507	655	INSULATION S102/SIC/AB312 GLZ (INORGANIC)
06508	321	COATING 856-301/FEP PR 856-204 TOPCOAT
06509	555	FILM W GHTLON 7400
06510	544	FILM LAR DRAFTING 1110
06511	417	CORD EVLAR BB2912 30/12X30
06512	458	FABRIC HERCULITE 80 NYLON
06513	770	MOLD COMPOUND POLYES/GL G100 BMC-LS
06514	736	LUBE EVERLUBE 620B1
06515	496	FABRIC SILICONE 7243G1523
06516	627	INSULATION FOAM POLYIMIDE 1720
06517	677	LACING TAPE NATURAL FIBER/WAX
06518	379	COATING PRIMER SAFETY WALK
06519	399	COMPOUND HEAT SINK SILICONE VB
06520	1,352	RUBBER SILICONE RTV 664
06521	442	FABRIC COTTON FR7A FIRE STOP
06522		DELETED SEE 06374
06523	124	ADHESIVE EPIBOND 1210A/C1210B
06524	756	LUBE RB-PREMIUM
06525	1,429	TAPE MYLAR M69 WITH ACRYLIC ADHESIVE
06526	150	ADHESIVE EPOXY 9-7844 B STAGE
06527	416	CORD FIBERGLASS/NEOPRENE
06528	374	COATING POLYURETHANE SATURN YELLOW 21517
06529	1,522	WEBBING STRAP NYLON FIRE/WATERPROOF
06530	44	ADHESIVE ARMSTRONG C7/W EPOXY
06531	1,456	TAPE SCOTCH Y966 ACRYLIC TRANSFER
06532	130	ADHESIVE EPOCAST 2201/C951
06533	447	FABRIC DRIGUARD 1527 POLYESTER
06534	421	CORE ARAMID PHENOLIC COATED GLASS FILLED
06535	1,330	RUBBER SILICONE CHOTHERM 1673R
06536	1,452	TAPE SCOTCH 79 FIBERGLASS
06537	668	LABEL IDENTIFICATION SCOTCHCLAD 8005 ADHESIVE/ ALUMINUM
06538	243	ADHESIVE SE871/CA2
06539	243	ADHESIVE SE851/CA2
06540	365	COATING NEXTEL 3101-C10
06541	300	CERAMIC BERYLLIUM OXIDE (INOR)
06543	565	GLASS OPTICAL (INORGANIC)
06544	380	COATING PT404A
06545	1,459	TAPE SCOTCHMARK 7883 POLYESTER
06546	1,499	TUBING SILICONE P/N 1665618
06547	1,533	WIRE ELEC TFE MINERAL FILLED
06548	443	FABRIC COTTON S55 F/PNH3 D/F
06549	443	FABRIC COTTON S65 F/PNH3 D/F
06550	758	MARKER SLEEVE KYNAR THERMOFIT
06551	588	INK K46 BLACK ON KYNAR/VITON
06552	1,536	WOOD SOFT COMMERCIAL
06553	276	ADHESIVE VERSILOK 528 ACRYLIC
06554	143	ADHESIVE EPOTEK 301 EPOXY
06555	5	ADHESIVE 17017 A/B POLYURETHANE
06556	1,353	RUBBER SILICONE RTV 738
06557	1,269	ROPE FIBERGLASS/TFE COATED SF200
06558	768	MOLD COMPOUND GLASS FILL 7721-3PPS
06559	257	ADHESIVE THERMAL 4952 EPOXY
06560	773	MOLD COMPOUND TFE/GLASS/MOS2
06561	351	COATING EPOXY/POLYAMIDE WHITE
06562	165	ADHESIVE FILM FM24 EPOXY
06563		DELETED SEE 06475
06564	113	ADHESIVE ECCOFOAM FPH12-4H
06565	710	LAMIN GRAPHITE/POLYIMIDE
06566	1,539	ZIPPER NOMEX/BRASS FIRE/WATER PROOF
06567	560	FLUOROLOY S TFE/CD SE SULFIDE
06568	1,518	WEBBING NOMEX 9981 FIREPROOFED
06569	1,518	WEBBING NOMEX 9476 FIREPROOFED
06570	452	FABRIC FIBERGLASS/CHLOROPRENE
06571	675	LACING TAPE HT-30 LOC B GREEN
06572	771	MOLD COMPOUND POLYETHYLENE
06573	762	MOLD COMPOUND ABS
06574	770	MOLD COMPOUND POLY-ACETAL
06575		DELETED SEE 00042
06576	619	INSULATION FOAM MINICELL L200 POLYETHYLN
06577	299	CERAMIC AB312 FABRIC/POLYSULFONE/FC723
06578	299	CERAMIC AB312 FABRIC/ACRYLIC/FC723
06579	1,325	RUBBER SILICONE 2850R
06580	533	FILM CAPRON 80
06581	7	ADHESIVE 322 EPOXY
06582	549	FILM POLYETHYLENE FR

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006696 3

MATCD	PAGE	DESIGNATION
06583		DELETED SEE 01018
06584	384	COATING SCOTCHGARD EC4101-C16
06585	545	FILM NM50-49 KAPTON GOLDIZED
06586	307	COATING 03-BL-51 POLYURETHANE FLAT BLUE
06587	101	ADHESIVE EA919 A/B EPOXY
06588	651	INSULATION GLASS WOOL F100
06589	591	INK MARKING SPECIAL 13
06590	229	ADHESIVE RESIN POLYESTER 988
06591	138	ADHESIVE EPON 828/DTA EPOXY GL FL
06592	1,522	WEBBING POLYESTER 562 PLASTIC
06593	386	COATING SILICONE GLASS/TETRABRN FIL
06594	467	FABRIC NICALON SILCN CARB INOR
06595	345	COATING ENAMEL 3C-31 POLYURETHANE WHITE
06597	765	MOLD COMPOUND EPIALL S-8723 EPOXY
06599		DELETED SEE 05844
06600	243	ADHESIVE SE881/CA2
06601	385	COATING SILICONE BLACK
06602	1,475	THREAD GLASS FIBER INORGANIC
06603	627	INSULATION FOAM POLYETHYLENE ETHAFOAM 220
06605	624	INSULATION FOAM PDL4034 FR POLYURETHANE
06606	1,493	TUBING NICALON
06607		DELETED SEE 05374
06608		DELETED SEE 06586
06609	102	ADHESIVE EA9320NA EPOXY
06610	375	COATING POLYURETHANE YELLOW 23785
06611	523	FASTENER VELCRO NYLON LOOP WITH PS 0102 ADHESIVE
06612	1,407	SPONGE RUBBER SILICONE F760
06613	1,351	RUBBER SILICONE RTV 630/50% OIL
06614	249	ADHESIVE SILGRIP SR6574 SILICONE
06615	553	FILM TEFLON FEP
06616	336	COATING CHOSHIELD EPOXY/AG FILLD
06617	72	ADHESIVE CHOBOND 1030/1086 SILICONE
06618	355	COATING HEXAMETHYLDISILAZNE Z6079
06619	655	INSULATION POWDER S102/AL203 INORGANIC
06620	628	INSULATION FOAM POLYIMIDE CHEMLON 701
06621	1,491	TUBING KYNAR CONVOLUTED BLACK
06622	219	ADHESIVE POLYFREEZE P146 EPOXY
06623	1,450	TAPE SCOTCH 60 TFE TEFLON/SILICONE
06624	310	COATING 421-03 GRAY
06629	350	COATING EPOXY SR1000 SOLDER RESIS
06633	1,416	TAPE DW204 TFE/SILICONE
06636	492	FABRIC POLYPROPYLENE 3X5WHDC
06639	1,495	TUBING POLYOLEFIN GPF135 HST
06641	297	CARBON GRAPHITE PUREBOND P9193
06642	1,518	WEBBING NOMEX/COATING FC4101-C-16
06643	614	INSULATION FOAM ECCOFOAM FPH 12-6H POLYURETHANE
06644	783	NYLON 6/6 ZYTEL 101
20001	757	LUBE TFE FLUOROCARBON TELOMER
20002	727	LUBE DRY ESNA 382
20003	727	LUBE DRY ELECTROFILM 2006 ORG
20005	1,301	RUBBER NEOPRENE 60382
20006	1,493	TUBING NT120 NEOPRENE HST
20007	447	FABRIC DRIGUARD 1227 NYLON/PVC
20008	453	FABRIC FRL 397.356 NOMEX
20009	1,364	RUBBER SPONGE NEOPRENE
20011	1,103	PLASTIC ROYALITE 57
20012	1,301	RUBBER NEOPRENE
20013	615	INSULATION FOAM ENSOLITE TYPE ALG PVC
20015	1,388	SEALANT GRAPHITAR 86/CARBON
20016	721	LEATHER GOATSKIN
20017	1,487	TUBING FP301 TYPE 2 POLYOLEFIN HS
20018	1,398	SHELL 405 CATALYST
20019	1,495	TUBING POLYOLEFIN GPR135 BLK
20021	1,497	TUBING POLYOLEFIN RT876 HST
20022	1,496	TUBING POLYOLEFIN RNF100
20023	659	INSULATION WIRE POLYOLEFIN/KYNAR
20024	1,508	VARNISH SYNTHITE AC41 CLF
20025	588	INK KX425 BLACK
20026	3	ACID LAURIC
20027	792	PARAFFIN WAX
20028	726	LUBE DRY DAG 250 ORGANIC BINDR
20029	1,362	RUBBER SILICONE SWS7220
20030	637	INSULATION FOAM PYRELL UNCOATED AND COATED RL4389
20031	652	INSULATION ISOMICA CL20 INORGANIC
20032	1,301	RUBBER NEOPRENE
20033	569	GREASE MOBIL 28
20034	729	LUBE DRY GRAPHITE/BINDEN PL94
20035	1,492	TUBING NEOPRENE RT510 HST
20036	1,494	TUBING POLYIMIDE ARAMID
20037	527	FELT ASBESTOS
20038	323	COATING ACRYLIC ENAMEL SW J5-5226
20039	324	COATING ACRYLIC ENAMEL SWF1081738
20040	323	COATING ACRYLIC ENAMEL SW CLEAR
20041	1,242	PLATE TERMINAL POLYESTER
20042	1,405	SPONGE RUBBER NEOPRENE
20043	685	LACQUER YELLOW
20046	1,103	PLASTIC ROYALITE 54
20047	597	INK TROJAN OPAQUE SILVER
20048	596	INK TROJAN OPAQUE BLACK
20049	181	ADHESIVE LCA4/BA5 EPOXY
20050	569	GREASE LUBRIPLATE 130A
20051	530	FELT WOOL
20052	655	INSULATION REIN CARBON/CARBON
20053	265	ADHESIVE TRABOND BB2112
20054	1,395	SEALANT THREAD VC3
20055	300	CERAMIC ALUMINO-SILICAT P1/2BC
20056	565	GLASS FLUORESCENT TUBE LAMP
20057	564	GLASS BOROSILICATE (INORGANIC)
20058	1,460	TAPE SILICONE SB1050Y/SB1050
20059	1,050	PLASTIC PLEXIGLASS 2 UVA
20060	66	ADHESIVE CEMENT PS18 ACRYLIC
20061	1,386	SEALANT CARBON PLUS BINDER P4229
20062	1,386	SEALANT CDJ83 CARBON PLUS BINDER
20063	360	COATING LACQUER PAINT QUICK DRY
20064	1,474	THERMOPLASTIC THERMAL STABILIZ
20065	428	DYE RED
20066	1,334	RUBBER SILICONE DMCPS1008
20067	283	BARIUM FERRITE (INORGANIC)
20068	1,392	SEALANT PUTTY 453 5 K36 BLK
20069	724	LITHIUM-STEARATE

MSFC-HDBK-527 REV F 9999942 0006697 5

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
20070	370	COATING POLYAMIDE RED 11136 EPOXY
20071	1,400	SILICA FUSED INORGANIC
20072	599	INSULATION ARMAFLEX (FR) NEOPRENE
20073	384	COATING SEMIGLOSS BLACK
20074	1,391	SEALANT POLYSULFIDE PROSEAL 890
20075	1,387	SEALANT EPOXY HARD FILTER
20077	1,326	RUBBER SILICONE 405
20081	107	ADHESIVE EC2158 EPOXY
20082	765	MOLD COMPOUND EPIALL 1914 EPOXY
20083		DELETED SEE 06467
20084	586	INK DEUTSCH DPS300
20085	586	INK DEUTSCH DPS147
20086	302	CERAMIC INSULATOR MATERIAL
20087	67	ADHESIVE CERAMIC APCO R310 EPOXY
20088	111	ADHESIVE ECCOBOND 56C/C9
20089	113	ADHESIVE ECCOBOND SOLDER 58
20090	739	LUBE GREASE BRAYCO 885B
20091	535	FILM ELVANOL 71-30 PVA
20092	13	ADHESIVE A4000 SILICONE
20093	1,283	RUBBER EPR E529-6
20094	1,450	TAPE SCOTCH 57 POLYESTER
20095	727	LUBE DRY ELECTROFILM 4306
20096	468	FABRIC NOMEX 2002/FLUOROSILICONE
20097	288	BRAKE MATERIAL F328 CORK COMP
20098	590	INK MARKING ALKYD BLACK
20099	631	INSULATION FOAM POLYURETHANE A206 TR
20100	666	LABEL IDENTIFICATION ALUMINUM FOIL PS MC1960010
20101	1,483	TUBING ACRYL-A-FA1 FIBERGLASS
20102	1,448	TAPE SCOTCH 54 POLYESTER PS
20103	45	ADHESIVE ARMSTRONG J1162 RESIN BASED
20104	51	ADHESIVE BONDMASTER E645
20105	1,261	POTTING COMPOUND SYLGARD 182
20106	602	INSULATION ELECTRICAL FORMVAR
20107	642	INSULATION FOAM SKYBOND POLYIMIDE
20109	381	COATING PYRE ML
20110	1,486	TUBING FIBERGLASS/EPOXY/PYRE ML COATED
20111	678	LACING TAPE NOMEX 431 SBR/ML
20112	1,418	TAPE FIBERGLASS COATED WITH PYRE ML
20113	1,486	TUBING FIBERGLASS/ACRYLIC
20114	470	FABRIC NOMEX 410 KAPTON/ML
20115	569	GREASE ANDOC C
20116	356	COATING HYDROPHILIC ZN O/SILICONE
20117	787	PAPER COPACO
20118	631	INSULATION FOAM POLYURETHANE FLEXIBLE
20119	680	LACING TAPE NYLON/DACRON LC136
20120	1,440	TAPE POLYESTER/GLASS 76593
20121	1,335	RUBBER SILICONE EXTREME LOW TEMPERATURE LOW TEMPERATURE HARDNESS SHORE "A" 65-75
20122	1,486	TUBING FIBERGLASS/SILICONE
20123	298	CELLULOSE ACETATE
20124	681	LACING TAPE POLYESTER AIR-TEX 217
20125	530	FIBER HE1051 GLASS/ACRY BIND
20126	585	INK CERAMIC WITH IRON OXIDE INORGANIC
20127	343	COATING DURACHEM 13905/DURACH 415
20128	99	ADHESIVE EA8 EPOXY
20129	1,365	RUBBER SYNTHETIC 11-102-1
20130	227	ADHESIVE R92039/H23490 EPOXY AB/BG
20131	340	COATING DC 630 SILICONE
20132	327	COATING BLACK OXIDE (INORGANIC)
20133	755	LUBE OIL VISCASIL 10000 SILICONE
20134	746	LUBE GREASE KRYTOX 250AB
20135	1,505	TUBING VITON V138A
20136	1,370	RUBBER VITON 1502 H41
20137	762	MOLD COMPOUND ARITEMP 221
20138		DELETED SEE 20017
20139	697	LAMIN EPOXY/GLASS G10
20140	451	FABRIC FIBERGLASS SILICONE/7010
20141	531	FILLER ACTROFILL 1241
20142	1,474	TETRALON TF 403-017
20143	372	COATING POLYURETHANE ER41.CLE
20144	148	ADHESIVE EPOXY
20145	530	FIBRE VULCANIZED GRADE CH
20146	568	GRAPHITAR GRADE 30A
20147	675	LACING TAPE HT-20 LOC A NOMEX
20148	234	ADHESIVE SCOTCHCAST 280 A/B
20149	243	ADHESIVE SCOTT 101
20150	1,443	TAPE REFLECTIVE
20151	1,383	RUBBER VITON V80-080/CHR 985
20152	681	LACING TAPE POLYESTER
20154	528	FELT NOMEX 62HT/14
20155	1,343	RUBBER SILICONE RTV 140
20156	391	COATING TYROLIT #GED-0 OPTICAL
20157	586	INK DEUTSCH DPS CL 1,3,4,5
20158	1,498	TUBING RESIN PAPER GRADE 22
20159	602	INSULATION ELECTRICAL RAG PAPER
20160	1,489	TUBING HYGRADE SR398 HB1
20161	726	LUBE DRY DRILUBE 822
20162	1,425	TAPE KAPTON/ACRYLIC K109
20163	208	ADHESIVE P82 C
20165	1,272	RUBBER BUTYL
20166	1,306	RUBBER NITRILE
20167	1,251	POTTING COMPOUND EE0004/HD3561
20168	1,245	POTTING COMPOUND C9W690/HD3615
20169	313	COATING 463-6-5 PRIMER/463-3-8 EPOXY
20170	324	COATING ALKYD GLOSS ENAMEL 12246
20171	52	ADHESIVE BONDMASTER M777 A/B EPOXY
20172	365	COATING NEXTEL 901P 1
20173	342	COATING DENNIS 1169 URETHANE A/B
20174	340	COATING DC 1204
20175	1,443	TAPE SAFETY WALK ANTI-SLIP
20176	1,268	ROD CP2-4289
20177	380	COATING PT401 RESIN/PT402 PRIMER
20179	724	LITHIUM HYDROXIDE INORGANIC
20180	583	INK BEE R222/T266 THINNER
20181	302	CHARCOAL (INORGANIC)
20182		DELETED SEE 05908
20183	150	ADHESIVE EPOXY B101
20184	338	COATING DAG195 CONDUCTIVE
20185	1,507	VARNISH GLYPTAL 1202 ALK
20187	581	IMPREGNANT BRAZING

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006698 7

MATCD	PAGE	DESIGNATION
20189	680	LACING TAPE NYLON 17X POLYAMID
20190	588	INK M219 VULCAN BLACK
20191	309	COATING 36231 ALKYD ENAMEL
20192	1,389	SEALANT MICROSEAL
20193	1,451	TAPE SCOTCH 7321/49/56X1302 MYLAR/SILICONE
20194	360	COATING LACQUER 604-37038
20195	113	ADHESIVE ECCOPRIME S11
20196	771	MOLD COMPOUND PROFAX 6527 POLYPROPYL
20197	30	ADHESIVE AMPHENOL 912 EPOXY/PHENOL
20198	106	ADHESIVE EC1357 NEOPRENE CEMENT
20199	1,327	RUBBER SILICONE 934 HEAT SINK
20200	762	MOLD COMPOUND 514AG10D DAP
20201	763	MOLD COMPOUND DAP 514AGID YELLOW
20203	587	INK F100 BLACK
20204	685	LACQUER GREEN COLOR 11105
20205	1,508	VARNISH SYNTHITE AC29-76
20206	726	LUBE DRY DAG 258 MOS2
20207	272	ADHESIVE URALANE 5753 POLYURETHANE
20208	532	FILM ADHESIVE XT40 110/234
20209	391	COATING URALANE 5750 A/B
20210	176	ADHESIVE IBM314 EPOXY
20211	103	ADHESIVE EA940 EPOXY
20212	767	MOLD COMPOUND FIBERITE FM4005 BLACK
20214	394	COATING WASH PRETREATMENT
20215	769	MOLD COMPOUND MELAMINE/GLASS GF-5
20216	188	ADHESIVE LOCTITE SCREWLOCK/T PRIMER
20217	329	COATING CAT-A-LAC 443-3-6
20218	360	COATING LACQUER STICK BLACK
20220	1,513	WAX ETHONE 18
20221	346	COATING ENAMEL WHITE
20222	137	ADHESIVE EPON 828/CAT U EPOXY
20223	337	COATING CORROSION PREVENTIVE
20224	720	LAQUER YELLOW
20225	1,306	RUBBER NITRILE
20226	280	ALCOHOL RESIN POLYVINYL COMPAR
20227	678	LACING TAPE NOMEX 950HOT16
20228	1,385	SAPPHIRE
20229	556	FINISH SYSTEM P213B
20230	739	LUBE GREASE BRAYCOTE 236
20231	1,307	RUBBER NITRILE MS29561-005
20232	482	FABRIC NYLON BUNA-N REINFORCED
20233	755	LUBE OIL PRESERVATIVE
20234	1,284	RUBBER EPR E798-70
20235	1,308	RUBBER NITRILE N766-75
20236	1,308	RUBBER NITRILE N741-75
20237	1,284	RUBBER EPR E740-75
20238	1,271	RUBBER BUNA N 5-565
20239	796	PENETRANT P-545/DEVELOP D-495A
20240	796	PENETRANT P-615/DEVELOP D-495A
20241	775	MOTOR GLOBE 43A1578
20242	311	COATING 453-4-BLUE POLYAMIDE SEMI-GLOSS EPOXY 212
20243	788	PAPER FILTER
20244	640	INSULATION FOAM SCOTT FILTER PPI XX
20245		DELETED SEE 05062
20246	568	GREASE AEROSHELL 17
20247	734	LUBE DRY ON METALLIC FASTENERS
20248	1,507	VARNISH INSULATING U86F
20249	757	LUBE WET 37987
20250	364	COATING NAZDAR ER111
20251	219	ADHESIVE POLYOLEFIN S1024
20252	1,461	TAPE TEFLON FEP 4043 AG INCONEL WITH T223 ADHESIVE
20254	380	COATING PT750/PT402 PRIMER
20255	684	LACQUER ACRYLIC
20256	1,507	VARNISH PHENOLIC M4068 CLEAR
20257	5	ADHESIVE 1872 EPOXY
20258	1,530	WIRE ELEC R4800/TY P222,P229
20259	630	INSULATION FOAM POLYURETHANE
20260	762	MOLD COMPOUND BAKELITE
20261	349	COATING EPOXY POLYAMIDE BLACK
20262	1,506	VARNISH BC354 CLEAR HI-TEMP
20263	556	FILTER MEDIA BACTERIA
20264	537	FILM HYTUFF MP2080 POLYURETHANE
20265	218	ADHESIVE POLYAMIDE SL6
20266	475	FABRIC NOMEX NON-WOVEN 141-329
20267	177	ADHESIVE ISOCHEM BOND 1308/95A6
20268	774	MOTOR ELECTRIC P/N 47A232920A
20269	789	PAPER KRAFT
20270	369	COATING POLANE F63CB2/V66V29
20271	680	LACING TAPE NYLON/RUBBER 18H
20272	344	COATING E755G EPOXY
20273	42	ADHESIVE ARMSTRONG A7-4322
20274	281	BAG CONTINGENCY P/N 47A232804
20275	1,498	TUBING RAYON
20276	1,386	SEALANT BARCO THERMOSET
20277	594	INK S1141 BLACK
20278	430	ELECTROLYTE KOH 6N (INORGANIC)
20279	688	LAMIN EPOXY MG2 NOVOLAC/PHENOL
20280	300	CERAMIC CAPACITOR P/N AOL0044
20281	285	BEARING BARDEN P/N 605172
20282	772	MOLD COMPOUND REXOLITE 1422 STYRENE
20283	371	COATING POLYURETHANE (ESTER)
20284	1,457	TAPE SCOTCHCAL 530 MYLAR
20285	1,462	TAPE TEFLON FLUOROLIN 101 WITH PS SILICONE ADHESIVE
20286	309	COATING 1295 EPOXY
20287	458	FABRIC GORTEX 2301
20288	418	CORD NOMEX 150 LB
20289	1,514	WEBBING DACRON 1287
20290	457	FABRIC GORTEX 1883C
20291	1,456	TAPE SCOTCHCAL 30 MYLAR
20292	475	FABRIC NOMEX S2352NBR FILTER
20293	1,434	TAPE NOMEX 9476
20294	474	FABRIC NOMEX HX-6157 SIZE F
20295	61	ADHESIVE CASTALL 343 EPOXY
20296	71	ADHESIVE CHEMOTEC 805/805B
20297	229	ADHESIVE RESIWELD 4 EPOXY
20298	649	INSULATION FOAM URETHANE SX136
20299	498	FABRIC T162-42
20300	546	FILM PERFLEX-E POLYURETHANE
20301	497	FABRIC SPANDEX NYLON

MSFC-HDBK-527 REV F ■ 9999942 0006699 9 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
20302	444	FABRIC COTTON STYLE 3715 COMBD
20303	493	FABRIC POPLIN COTTON AND DACRON
20304	1,478	THREAD NYLON STRETCH 7
20305	266	ADHESIVE TYGOBOND 50
20306	1,475	THREAD COTTON 2 CORE
20307	482	FABRIC NYLON CHIFFON
20308	554	FILM TUFTANE 410 POLYURETHANE
20309	481	FABRIC NYLON 6611 OXFORD YELLOW
20310	467	FABRIC NEOPRENE RIPSTOP COATED
20311	214	ADHESIVE PLIOBOND
20312	690	LAMIN EPOXY/GLASS
20313	644	INSULATION FOAM SYNTACTIC EPON 815/KEVLAR
20314	486	FABRIC ORTHO 116
20315	1,516	WEBBING KEVLAR 1758
20316	671	LACING CORD KEVLAR
20317	465	FABRIC KEVLAR/NOMEX STYLE 145
20318	1,480	THREAD TEFLON S302 SIZE B
20319	1,478	THREAD NYLON TCA70143 SIZE B
20320	523	FASTENER VELCRO NYLON LOOP V22-90-W48 BACKING URETHANE FOAM
20321	721	LEATHER DEERSKIN
20322	1,434	TAPE NYLON 6707
20323	1,404	SPONGE RUBBER LATEX KOYLON
20324	1,401	SLEEVING DACRON WOVEN FABRIC
20325	354	COATING HELASTIC 23GD102
20326	272	ADHESIVE UR1087 VINYL/URETHANE
20327	274	ADHESIVE URETHANE 1246 A/B
20328	1,537	YARN STYLE 7511
20329	462	FABRIC KEVLAR 152 KNIT
20330	434	FABRIC AB06-80MZL MULTI-FIL
20331	502	FABRIC UTOPIA STYLE #540982
20332	1,521	WEBBING POLYESTER 1749
20333	552	FILM SARAN 8 CLEAR
20334	597	INK TYPEWRITER RIBBON
20335	1,440	TAPE POLYESTER LOOP 2297
20336	681	LACING TAPE POLYESTER 2298
20337	1,479	THREAD POLYESTER SIZE E
20338	481	FABRIC NYLON A2634/B 3.8 OZ
20339	413	CONNECTOR POLYPROPYLENE #6151
20340	500	FABRIC TEFLON T-83-54
20341	473	FABRIC NOMEX HF9254 3.2 OZ
20342	464	FABRIC KEVLAR STYLE 202 3.2 OZ
20343	483	FABRIC NYLON RIPSTOP UNCOATED
20344	528	FELT NOMEX 4.5 OZ/SQ YD
20345	1,380	RUBBER VITON V2-5159
20346	434	FABRIC 6007-1-1-54 HEAVY WT
20347	1,519	WEBBING NYLON 7774
20348	593	INK PM39 BLACK
20349	589	INK MARKING 44
20350	595	INK SHARPIE PEN 59
20351	184	ADHESIVE LOCTITE 271 THREADLOCK
20352	357	COATING IMPREGNANT GLOVE POLYURETHANE
20353	747	LUBE GREASE PETROLATUM/MOS2
20354	391	COATING UNICOAT 501
20355	42	ADHESIVE ARMSTRONG A5-4318/H3486 EPOXY
20356	1,466	TAPE TUCK 24
20357	173	ADHESIVE GLYPTAL 7526F
20358	162	ADHESIVE FE7119
20359	117	ADHESIVE EMX138 A/B
20360	438	FABRIC BETA/SILICONE 5035
20361	345	COATING ENAMEL 479
20362		DELETED SEE 20289
20363	467	FABRIC NO T-261-36 TEFLON
20364	451	FABRIC FELT 5913-07 NOMEX
20365	956	PLASTIC LEXAN 500 POLYCARBONATE
20366	1,360	RUBBER SILICONE SE550
20367	1,359	RUBBER SILICONE SE4552
20368	727	LUBE DRY ELECTROFILM 1000 MOS2
20369	99	ADHESIVE EA6 EPOXY
20370	955	PLASTIC LEXAN 141 POLYCARBONATE
20371	1,243	POLYPROPYLENE STYLE 9079
20372	1,517	WEBBING NEOTEX 12
20373	420	CORD SHOCK RUBBER/KEVLAR/COTTON
20374	383	COATING RUSTOLEUM
20376	500	FABRIC TEFLON T21-42
20377	346	COATING ENAMEL BLACK
20378		DELETED SEE 20755
20379	445	FABRIC DACRON 15292
20380	438	FABRIC BIAS PLY COATED
20381	1,516	WEBBING KEVLAR FRL-S-196
20382	666	LABEL IDENTIFICATION 126 FABRIC
20383	1,429	TAPE MYLAR PS ADHESIVE
20384	543	FILM MYLAR ALUMINIZED
20385	1,476	THREAD KEVLAR
20386	364	COATING NEDOX SF2 TEFLON
20387	229	ADHESIVE RESIWELD 7004
20388	491	FABRIC POLYESTER NON-WOVEN
20389	1,428	TAPE LOOP-TAPE KEVLAR 2176
20390	1,477	THREAD NYLON
20391	1,492	TUBING LATEX RUBBER
20392	1,293	RUBBER FLUOROSILICONE NE7070G
20393	1,293	RUBBER FLUOROSILICONE NE6060
20394	733	LUBE DRY MOLYKOTE L
20395	1,293	RUBBER FLUOROSILICONE NE4240
20396	1,343	RUBBER SILICONE RTV 156
20397	733	LUBE DRY MOLYKOTE M8800
20398	771	MOLD COMPOUND POLYURETHANE CASTABLE
20399	554	FILM TUFTANE 310 POLYURETHANE
20400	454	FABRIC FYPRO TREATED NOMEX
20401	721	LEATHER NAME PATCHES
20402	1,393	SEALANT SCOTCHSEAL EC1103
20403	205	ADHESIVE OPTICAL CEMENT
20404	1,338	RUBBER SILICONE NE6070
20405	1,395	SEALANT THREAD LOCKING
20406	480	FABRIC NOMEX/ZEPEL COATED
20407	441	FABRIC COTTON FLAME RETARDANT
20408	287	BRAID ELASTIC POLYESTER/RUBBER
20409	494	FABRIC SATEEN COTTON 40Z/YD
20410	1,540	ZIPPER POLYESTER/NYLON COGS
20411	418	CORD NOMEX/NEOPRENE COATED 1/8 IN

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006700 1

MATCD	PAGE	DESIGNATION
20412	282	BAG PLASTIC INTERLOCKING CLOSR
20413	442	FABRIC COTTON INTERFACING
20414	430	EMBLEM CLOTH NASA
20415	430	EMBLEM CLOTH US FLAG
20416	1,477	THREAD NOMEX 50/3 TYPE 450
20417	1,385	SCREEN NYLON MESH
20418		DELETED SEE 05298
20419	626	INSULATION FOAM POLYETHER URETHANE RIGID
20420	1,356	RUBBER SILICONE RTV SWS930
20421	720	LAMP INCANDESCENT GLASS/METAL
20422	324	COATING AERO-CATICOAT
20423	326	COATING ASTRODYNE 922
20424	363	COATING MO-201 EPOXY
20427	1,497	TUBING POLYVINYLCHLORIDE (PVC)
20428	415	CORD DACRON BRAIDED TROLL 70LB
20429	674	LACING TAPE GORTEX .062 DIA
20430	1,427	TAPE LOOP-TAPE GORTEX
20431	1,416	TAPE ELASTIC .75 WIDE
20432	466	FABRIC MARQUISETTE NYLON N-44
20433		DELETED SEE 05286
20434	1,325	RUBBER SILICONE 382 MEDICAL SI
20435	550	FILM POLYURETHANE HITUFF MP1880
20436	1,351	RUBBER SILICONE RTV 616
20437	1,272	RUBBER BUNA S
20438	552	FILM STABILENE DIAZO
20439	548	FILM POLYETHYLENE
20440	368	COATING PHENOLIC BASE
20442	346	COATING ENAMEL YELLOW
20443	21	ADHESIVE ABLEFILM 504 EPOXY
20444	699	LAMIN EPOXY/GLASS SVHS 8091T2
20445	699	LAMIN EPOXY/GLASS SVHS 8091T3
20446	699	LAMIN EPOXY/GLASS SVHS 8091T4
20447	587	INK EPOXY 128-45C BLACK
20448	288	BRAKE MATERIAL S451
20449	11	ADHESIVE 84706
20450	1,410	STRAP ELASTIC FSN 8305
20451	1,303	RUBBER NEOPRENE MOUTHPIECE
20452	312	COATING 463-3-100/C-118 PRIMER WHITE
20453	157	ADHESIVE EPOXYLITE 8712 COATING
20454	488	FABRIC PBI S-141 FX WEBBING
20455	152	ADHESIVE EPOXY PATCH KIT 0151 CLEAR A/B
20456	1,442	TAPE POLYPROPYLENE P910
20457	771	MOLD COMPOUND POLYPRO
20458	554	FILM THERMOFILM 4500-5
20459	36	ADHESIVE ARALDITE 101
20460	393	COATING VISANEL NON-GLOSS
20461	726	LUBE DRY DRILUBE 1A
20462	502	FABRIC VELVETEEN
20463	322	COATING ACETATE BUTYRATE
20464	431	ERASER RUBBER PINK PEARL
20465	60	ADHESIVE CANADA BALSAM
20466	1,367	RUBBER TROLEN
20467	570	HARDENER AGOMET
20468	564	GASKET SIMRIT
20469	734	LUBE DRY PT101
20470	525	FASTENER VELCRO POLYESTER HOOK H592
20471	1,475	THREAD GLASS PTFE COATED
20472	114	ADHESIVE ECCOSIL 4712
20473	1,390	SEALANT POLYSULFIDE EC101
20474	1,262	POWDER BIOSORB B210
20475		DELETED SEE 05780
20476	466	FABRIC NAMETAGS
20477	358	COATING KRYLON 1301 CLEAR
20478	1,419	TAPE FR357 ADHESIVE WITH BACKING
20479	447	FABRIC DPB 65-45 KEVLAR 29
20480	138	ADHESIVE EPON 828/EM308 EPOXY
20481	9	ADHESIVE 4144/3496 EPOXY
20482	301	CERAMIC DUROCK 101
20483	529	FELT NOMEX STYLE 22NX
20484	185	ADHESIVE LOCTITE 504
20485	184	ADHESIVE LOCTITE 242
20488	588	INK LUMOCOLOR 317
20489	592	INK PEN 60 SILVER
20490		DELETED SEE 06644
20491	1,522	WEBBING POLYESTER ELASTIC
20492	630	INSULATION FOAM POLYURETHANE 2.7LB/CU FT
20493	588	INK KP402 URETHANE WHITE T102
20494	1,293	RUBBER FLUOROSILICONE NE7075
20495	529	FELT TFE
20496	465	FABRIC LYCRA SPANDEX
20497	1,465	TAPE TFE
20498	418	CORD NYLON
20499	53	ADHESIVE BOSTIK 1205/B9072
20500	176	ADHESIVE HYLENE M50
20501	354	COATING HELASTIC 2010
20502	1,478	THREAD NYLON E.O.D. COLOR
20503	768	MOLD COMPOUND GEON
20505	1,427	TAPE LOOP-TAPE KEVLAR 1759
20506	794	PEN PENTEL S520 RED
20507	587	INK INDELIBLE MARKING
20508	1,305	RUBBER NEOPRENE/HELMET LINER
20509	351	COATING F/N-6620F EPOXY
20510	351	COATING F/N-65208 PRIMER EPOXY
20511	1,275	RUBBER CHLOROPRENE CPD 2408A
20512	751	LUBE OIL CORR INHIBIT X90315
20513	419	CORD NYLON G1008 1/8 DIA
20514	381	COATING QUICK 65918
20515	588	INK JUSTRITE INDELIBLE
20516	441	FABRIC COTTON FLAME RETARD 4 OZ
20517	781	NOSECLIP P/N 85103531
20518		DELETED SEE 63120
20519	1,399	SHROUD CUTTER P/N60C6037
20520	1,117	PLASTIC SHEET ABS BLACK
20521	286	BLANKET SURVIVAL SPACE BRAND
20522	566	GLOVE GS/FRP-2
20523	482	FABRIC NYLON DACRON COATED
20524	1,481	TISSUE TOILET SINGLEFOLD
20525	442	FABRIC COTTON HANDKERCHIEF
20526	442	FABRIC COTTON POCKET CWG
20527	1,390	SEALANT POLYSULFIDE PR1201HT

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
20528	1,391	SEALANT POLYURETHANE PR1656
20529	367	COATING PEDIGREE 923 EPOXY VARNISH
20530	660	IRON OXIDE (INORGANIC)
20531	594	INK RETARDER PAT715/T950
20532	692	LAMIN EPOXY/GLASS 7781/550/P650M
20533	1,303	RUBBER NEOPRENE NS105B
20534	620	INSULATION FOAM MOLECULON FR302 POLYURETH
20535	634	INSULATION FOAM POLYURETHANE VALSALVA
20536	765	MOLD COMPOUND E-3938C GLASS/EPOXY
20537	595	INK SILICONE BASE
20538	150	ADHESIVE EPOXY 94318
20539	1,326	RUBBER SILICONE 50
20540	417	CORD KEVLAR B275
20541	342	COATING DERUSTO 511 EPOXY WHITE
20542	348	COATING EPOXY ENAMEL 66208 WHITE
20543	426	DEODORANT SOLID UNSCENTED
20544	423	CREME NIVEA SKIN CARE
20545	425	DEODORANT SOLID ANTI-PERSPIRNT
20546	357	COATING INDOTHANE 441-1C-41 WHITE
20547	719	LAMIN/EPOXY/GLASS EPON 815/GLASS 7781/DTA
20548	720	LAMIN/EPOXY/GLASS/EPON 815/GLASS 112/DTA
20549	695	LAMIN EPOXY/GLASS EPON APCO 434/SONITE 41
20550	714	LAMIN POLYESTER/GLASS HETRON 92
20551	132	ADHESIVE EPON 815/DTA
20552	133	ADHESIVE EPON 815/DTA/PHENOLIC F
20553	325	COATING APCO 434/SONITE 41 EPOXY
20554	1,439	TAPE PAPER DOUBLEFACE PSA
20555	1,474	TEMP SENSITIVE DOTS-PROPRIETAR
20556	1,421	TAPE G407810 VACUUM DEPOSITED ALUMINUM 1 MIL KAPTON WITH 1 MIL SILICONE ADHESIVE
20557	578	HOSE SILICONE MS70G31
20558	569	GREASE DC40 SILICONE
20559	1,402	SOCKS TUBE 90% COTTON 10%NYLON
20560	1,318	RUBBER SILASTIC 55U SILICONE
20561	438	FABRIC BETA/SILICONE 10535/9362
20562	283	BATTERY DURACELL HG SIZE AA/ZM9
20563	1,441	TAPE POLYIMIDE/SILICONE K100
20564	1,292	RUBBER FLUOROSILICONE L737-65
20565	364	COATING N136 EPOXY ENAMEL
20566	237	ADHESIVE SCOTCHGRIP EC1300L
20567	719	LAMIN VANOXY 128/VERSAMID 140F
20568	476	FABRIC NOMEX TRICOT STYLE 240
20569	471	FABRIC NOMEX 7878-18 BLUE
20570	447	FABRIC DUCK COTTON TY 3
20571	721	LEATHER COWHIDE BLACK 3 OZ
20572	631	INSULATION FOAM POLYURETHANE 3-4LBS
20573	267	ADHESIVE UNIROYAL 6100
20574	615	INSULATION FOAM ENSOLITE TYPE AH
20575	476	FABRIC NOMEX SIMPLEX
20576	1,361	RUBBER SILICONE SI644-01
20577	1,433	TAPE NOMEX 1229
20578	1,496	TUBING POLYOLEFIN RT1304 HST
20579	483	FABRIC NYLON URETHANE COATED
20580	70	ADHESIVE CHEMLOK 304
20581	789	PAPER KLEENEX TISSUE PACK
20582	544	FILM MYLAR MIRROR REFLECT
20583	1,482	TOWELS KAYDRY PAPER
20584	284	BATTERY NI/CD RECHARGE 7.0SC
20585	284	BATTERY NI/CD CADNICA W10000M
20586	1,269	RUBBER 4930-00-946-2916
20587	283	BATTERY DURACELL HG RM12R 1.35
20588	758	MARKING CRAYON 900 YELLOW
20589	758	MARKING CRAYON 900 GRAPHITE BLK
20590	759	MARKING CRAYON 904 CARBON BLK
20591	1,262	POWDER 8804 STAMPING BLUE
20592	682	LACING TAPE POLYESTER RED
20593	672	LACING TAPE BLACK
20594	491	FABRIC POLYESTER KNIT
20595	1,479	THREAD POLYESTER GOLD
20596	1,479	THREAD POLYESTER STEEL SIZE F
20597	1,479	THREAD POLYESTER BLACK FF
20598	423	CREAM SHAVE BRUSHLESS
20599	423	CREME SHAVE BRUSHLESS
20600	1,368	RUBBER VACUBASE
20601	1,522	WET WIPES
20602	1,482	TOWELS 78% COTTON/22% POLYESTER
20603	795	PENCIL STYPTIC
20604	423	CREAM HAND/KERI
20605	425	DEODORANT DIAL SOLID
20606	425	DEODORANT OLD SPICE SOLID
20607	425	DEODORANT ENGLISH LEATHR SOLID
20608	425	DEODORANT BRITISH STERLG SOLID
20609	664	KNIFE SWISS ARMY 136KMAU
20610	795	PEN SPACE B1-PR4F REFILL BLACK
20611	1,409	STAIN TRANSPARENT
20612	285	BATTERY THIONYL CHLORIDE
20613	495	FABRIC SHIRT JOE NAMATH
20614	415	CORD BOOT LACES
20615	495	FABRIC SHORTS BOXER
20616	499	FABRIC TEE SHIRT
20617	495	FABRIC SHORTS JOCKEY
20618	1,401	SLEEVING NOMEX BRAID
20619	1,293	RUBBER FLUOROSILICONE NE6072
20620	267	ADHESIVE U500-25 EPOXY
20621	759	MASCARA SUPER RICH
20622	1,411	TAMPONS DEODORANT SUPER PLUS
20623	757	MAKEUP CHEEKCOLOR POWDER
20624	724	LIPSTICK NATURAL WONDER
20625	432	EYE MAKEUP REMOVER 30 SEC
20626	432	EYE SHADOW CREAM-ON SUPER LUST
20627	432	EYE LINER
20628		DELETED SEE 20520
20629	411	CONNECTOR JUNCTN CTV122E05/10
20630	287	BRAID NOMEX COVER/HARNESS
20631	584	INK BIC MARKING PM DELUX
20632	699	LAMIN EPOXY/GLASS SVHS 8091T13
20633	699	LAMIN EPOXY/GLASS SVHS 8091T11
20634	689	LAMIN EPOXY/CAB-O-SIL
20635	549	FILM POLYURETHANE 5 MIL
20636	549	FILM POLYURETHANE 10 MIL

MSFC-HDBK-527 REV F 9999942 0006702 5

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
20637	1,375	RUBBER VITON E43060
20638	1,324	RUBBER SILICONE 15130
20639	1,363	RUBBER SILICONE TA96
20640	1,426	TAPE KEVLAR 2176-1
20641	463	FABRIC KEVLAR 2176
20642	468	FABRIC NOMEX 200 DENIER
20643	429	ECCOGEL 1265/CABOSIL
20644	408	CONNECTOR ELECTRICAL
20645	429	ECCOGEL 1265/EPOXY
20646	550	FILM POLYURETHANE GLOVE BLADDER
20647	1,405	SPONGE RUBBER NEOPRENE OPEN CELL 2-S-198
20648	1,360	RUBBER SILICONE SE565
20649	577	HOSE REDAR A111331-1 VITON B
20650	1,358	RUBBER SILICONE S899-50
20651	1,535	WIRE MAGNET P/N 1600E-056B-013
20652		DELETED SEE 06409
20653	759	MASCARA LONG-NLUSH BLACK/BROWN
20654	759	MASCARA EVERY LAST LASH/BROWN
20655	759	MASCARA EXTRA LNGTH WITH SEALER
20656	759	MASCARA RICH LASH THICKENING
20657	432	EYE SHADOW BLUEBERRY
20658	1,481	TISSUE DRY AND POLISHING
20659	497	FABRIC SPANDEX 90221/FIN 1635
20660	667	LABEL IDENTIFICATION ILC UNSPRAYED NOT TYPED
20661	225	ADHESIVE PUREBOND P658RC
20662	549	FILM POLYETHYLENE8135-00-006-5962
20663	1,415	TAPE CORRECT 7510-00-634-5110
20664	508	FASTENER VELCRO ADHESIVE 45
20665	584	INK BIC AF69
20666	721	LEATHER SUPER SHENE FINISH 2002
20667	1,399	SHOE SPRAY BLACK 317
20668	1,265	RAZOR SAFETY SUPER 84
20669	286	BLADE RAZOR DOUBLE EDGED PLATE
20670	1,482	TOOTHPASTE CREST
20671	1,481	TOOTHBRUSH ORAL B-40
20672	425	DEODORANT MITCHUM STICK
20673	723	LIPBALM CHAPSTICK
20674	723	LIPBALM BLISTIK
20675	724	LIPBALM CONSTANT CARE
20676	1,536	WRISTLETS P/N A7L-101121-01
20677	1,398	SHOE HEEL NEOLITE
20678	1,399	SHOE SOLE NEOPRENE 9 IRON
20679	567	GLOVE PVC DISPOSABLE
20680	1,401	SOAP IVORY 2OZ
20681	557	FLOSS DENTAL NYLON UNWAXED
20682	1,398	SHAVER WIND-UP 122A
20683	1,411	SUNGLASSES AND CASE
20684	423	COVER EYE CELEBRITY SLEEP REST
20685	429	EARPLUGS 4560
20686	557	FLASHLIGHT
20687	423	CUFFS ROLL-ON
20688	669	LABEL IDENTIFICATION UCD CLIPS 0109-22061-01
20689	289	BRUSH STYLING ALUMINUM JATCO
20690	386	COATING SILICONE SR80 RESIN
20691	342	COATING DIMETCOTE 3/AMERCOTE 383HS
20692	957	PLASTIC LEXAN 9410 WHITE POLYCARBONATE
20693		DELETED SEE 20384
20694	427	DISH SOAP HSB 2
20695	150	ADHESIVE EPOXY DGBA
20696	570	HAMMER BALLPEEN P/N BP-N-4A
20697	432	EYE SHADOW CREME-SIL FROSTBLUE
20698	432	EYE SHADOW CREME SKYLIGHT BLUE
20699	433	EYE SHADOW LT BLUE
20700	1,361	RUBBER SILICONE SM3500-53
20701	1,361	RUBBER SILICONE SM3500-66
20702	1,454	TAPE SCOTCH Y427 ALUMINUM WITH ACRYLIC ADHESIVE
20703	684	LACING TAPE TG-30 20AWG
20704	254	ADHESIVE SUPERBONDER 496 ACRYLIC
20705	275	ADHESIVE VELODUR METAL/EPOXY
20706		DELETED SEE 20646
20707	698	LAMIN EPOXY/GLASS RP4002A
20708	617	INSULATION FOAM HYPOL FHP3000 POLYURETHANE
20709	669	LABEL PAPER JCP-E20
20710	603	INSULATION FOAM ARMAFLEX 22 NEOPRENE
20711	40	ADHESIVE ARMSTRONG 520 NEOPRENE
20712	43	ADHESIVE ARMSTRONG A8-4219/H2-3404 EPOXY
20713	479	FABRIC NOMEX/TFE COATED
20714	489	FABRIC PBI S-210 FX 4.80Z/SQYD
20715	289	BUTTON IRIDES WHT PE 21/4 HOLE
20716	230	ADHESIVE RESIWELD 7004/5% CABOSIL
20717	1,377	RUBBER VITON NE8477
20718	283	BATTERY DRY K308A P4-01-0008
20719	283	BATTERY DRY BA1568/U 14 VOLTS
20720	244	ADHESIVE SH238
20721	366	COATING OPTICAL MAG FLUORIDE-INORGANIC
20722	366	COATING OPTICAL ZN SULFIDE-INORGANIC
20723	366	COATING OPTICAL SI MONOXIDE-INORGANIC
20724	372	COATING POLYURETHANE PLENUM FILM
20725	379	COATING PRIMER SS4120
20726	1,453	TAPE SCOTCH 950 ACRYLIC TRANSFER
20727	591	INK NAZDAR ER112 EPOXY
20728	769	MOLD COMPOUND NORYL SE-1
20729	445	FABRIC CSPP1 WHITE
20730	1,521	WEBBING POLYESTER 2276 ELASTIC
20731	1,396	SEALANT VIBRA-TITE ADHESIVE
20732	416	CORD ELASTIC EXERCISER
20733	484	FABRIC NYLON URETHANE COATED 6611
20734	1,411	SWAB DISPOSABLE
20735	790	PAPER PHOTOGRAPHIC
20736		DELETED SEE 06386
20737	1,434	TAPE NOMEX 9650
20738	489	FABRIC PBI S111 FX WEBBING
20739	489	FABRIC PBI S151 FX WEBBING
20740	792	PEN AG-7 BLK MED POINT ANTI-G
20741	1,417	TAPE FABRIC C516 VINYL COATED
20742	528	FELT NOMEX
20743	595	INK SERIES 4500 45NL75/82853
20744	794	PEN PARKER 6-234-8 BLACK
20745	372	COATING POLYURETHANE PLENUM .0575THK
20746	335	COATING CHEMGLAZE Z853/9986

MSFC-HDBK-527 REV F ■ 9999942 0006703 7 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
20747	335	COATING CHEMGLAZE Z752 POLYURETHANE 9924
20748	335	COATING CHEMGLAZE Z651 POLYURETHANE 9924
20750	330	COATING CHEMGLAZE A170
20751	1,449	TAPE SCOTCH 5480 TEFLON
20752	626	INSULATION FOAM POLYCARBONATE 141/FLC95/BLK701
20753	1,187	PLASTIC TORLON 4301 POLYIMIDE-AMIDE
20754	626	INSULATION FOAM POLYETH L200/L3203-6 CTG
20755	1,497	TUBING POLYURETHANE NOC
20756	1,529	WIRE ELEC PVC
20757	1,384	SAFETY WALK RESIN P/S CORK/RUB
20758	280	ANTI-FOG SOLUTION P/N 350AF
20759	491	FABRIC POLYESTER URETHANE COATED
20760	789	PAPER LINT FREE
20761	492	FABRIC POLYESTER/COTTON
20762	1,299	RUBBER LATEX NATURAL
20763	1,463	TAPE TEFLON TY10 SILICONE
20764	453	FABRIC FR COTTON 7 OZ/SQ YD
20765	1,384	SANITIZER AMMONIUM STERICIDE
20766	1,448	TAPE SCOTCH 5201-8 EMBOSSING
20767	489	FABRIC PBI S-165 FX
20768	573	HOSE FEDFLEX SGG
20769	1,416	TAPE DUCT CLOTH ST260
20770	60	ADHESIVE CASTALL 1520/E34 EPOXY
20771	1,513	WAX ENTEK 18 WATER BASE
20772	1,415	TAPE CORRECTION
20773	586	INK DURAGRAPH B20082 AL RED
20774	1,403	SPHERES FILTER EPOXY UMPQUA
20775	133	ADHESIVE EPON 820/CAT U EPOXY
20776	1,263	POWDER TALC
20777	167	ADHESIVE FLEXCRAFT 868 URETHANE/VINYL
20778	1,319	RUBBER SILASTIC DC55
20779	279	ADHESIVE ZIPGRIP 10
20780	1,323	RUBBER SILICONE 'E'
20781	449	FABRIC DURETTE 420-11
20782	551	FILM RUCOTHANE CO-A5069 POLYURETHANE
20783	399	COMPOUND ANTI-SEIZE METHOCEL/SILICONE CARB
20784	655	INSULATION REIN CARBON/CARBON/A-COATED
20785	684	LACQUER CELLULOSE NITRATE YELLOW
20786	684	LACQUER ACRYLIC NIT OCEL 17038
20787	684	LACQUER CELLULOSE N TRATE BLAK
20789	685	LACQUER VHT1200F SP101 17875
20790	685	LACQUER VHT 1200F SP102 17038
20791	1,428	TAPE LOOP-TAPE NOMEX
20792	476	FABRIC NOMEX S619/ZEPEL 69878
20793	453	FABRIC FLANNEL 545 COTTON WHITE
20794	248	ADHESIVE SILGRIP SR529 SILICONE
20795	387	COATING SILICONE WHITE PT805
20796	688	LAMIN EPOXY/ARAMID F164
20797	168	ADHESIVE FLUOROCARB 6700 COPOLYMR
20799	370	COATING POLYIMIDE BLACK 37038 EPOXY
20818	426	DESICCANT SILICA GELL
20819	762	MOLD COMPOUND CELLU/ACETATE BUTYRAT
20820		DELETED SEE 60596
20822	114	ADHESIVE ECCOSIL 4952
20823	154	ADHESIVE EPOXY SILVER FILLED K20

MATCD	PAGE	DESIGNATION
20848	282	BANDAGE MOLESKIN
20874	286	BLADDER NEOPRENE 3N868 NO4/6
20875	584	INK BLADDER MARKING URETHANE
20877	1,530	WIRE ELEC RAYCHEM 44 ALL GAGES
20879	713	LAMIN PHENOLIC/GLASS
20880	1,462	TAPE TEFLON FEP SILICONE ADHESIVE
20881	1,462	TAPE TEFLON FEP WITH Y966 TRANSFER ADHESIVE
20882	1,462	TAPE TEFLON FEP AL/AG Y966 ADHESIVE
20883	538	FILM KAPTON ALUMINIZED
20884	553	FILM TEFLON FEP METALIED AL/AG
20885	1,424	TAPE KAPTON AL/AU WITH Y966 ADHESIVE
20886		DELETED SEE 06531
20887	771	MOLD COMPOUND POLYETHYLENE THERMAL ST
20888	1,538	Z MATL/PART TO BE CHGD-NONMETL
20889	598	INK WORNOW SERIES M GR/RED/BLU
20890	668	LABEL IDENTIFICATION POLYESTER/RAYON
20891	1,439	TAPE POLYESTER 415/ACRYLIC ADHESIVE
20892	615	INSULATION FOAM EPOXY SYNTACTIC MODIFIED
20894	548	FILM POLYESTER ALUMINIZED
20895	483	FABRIC NYLON MESH NON-MELTING
20896	549	FILM POLYIMIDE ALUMINIZED
20899	381	COATING PYROMARK 2500 HE BLACK
20900	1,537	Z 40MXXXXX CONNECTOR
20901	1,537	Z EEE NO OPERATIONAL PART
20902	1,537	Z EEE OPERATIONAL PART
20905	771	MOLD COMPOUND POLYPHENYLENE OXIDE
20908	1,530	WIRE ELEC PVC-A
20911	434	FABRIC 6009-1-1
20920	493	FABRIC POLYPROPYLENE 4X5 WHDC
20925	1,476	THREAD NOMEX
30118	660	K-6 ALLOY TEST DISCS
30138		DELETED SEE 20017
30888	1,538	Z MATL/PART TO BE CHGD-METAL
30999	1,538	Z METALLIC MATL REQ EVAL
40000	1,538	Z ONE TIME USE/INSUF DATA
50075	1,537	Z MATL AGED OR HEAT TREATED
60051	1,263	PRIMER ZINC-SELE 9334 GREEN
60052	350	COATING EPOXY WHITE 9392/10A00528
60054		DELETED SEE 06467
60056	1,390	SEALANT POLYSULFIDE PR1422
60057	313	COATING 463-6-3 GREEN EPOXY
60058	311	COATING 443-3-1 WHITE EPOXY
60059	302	CETYL ALCOHOL-FASTENR LUB ONLY
60060	1,363	RUBBER SILICONE THERMAL CONDUCTIVE
60062	341	COATING DC 93-104 SILICONE
60063	708	LAMIN FIBERITE MX4926
60064	708	LAMIN FIBERITE MX2652
60065	101	ADHESIVE EA913 EPOXY
60067	1,367	RUBBER TR3005
60069	1,470	TEFLON PTFE 8573
60070	708	LAMIN FIBERITE MXB6020
60071	421	CORK AB 600
60072	368	COATING PHENOLIC SC 1008
60074	352	COATING FUNGICIDAL
60075	713	LAMIN PHENOLIC/COTTON TYPE FBM

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006704 9

MATCD	PAGE	DESIGNATION
60076	287	BORON 2A
60077	287	BORON GRANDULES
60078	67	ADHESIVE CERAMIC TYCEMENT UF3206
60079	163	ADHESIVE FIBER RESIN 55-9
60080	629	INSULATION FOAM POLYSTYRENE LOW DENSITY FR
60081	323	COATING ACRYLIC EMUL-EXT-WHITE
60083	696	LAMIN EPOXY/GLASS FF91
60084	346	COATING ENAMEL LUSTERLESS STYRENE ALKYD
60088	67	ADHESIVE CERAMIC MITHRA 200
60089	626	INSULATION FOAM POLYESTER OPEN CELL
60090	741	LUBE GREASE BRAYCOTE 6275
60091		DELETED SEE 06326
60093	1,264	PROPELLANT TPH1148
60094	1,264	PROPELLANT TPH1154
60095	1,264	PROPELLANT LINER UF2137
60098	1,300	RUBBER NBR INSULATION
60099	562	GAS HELIUM
60100	562	GAS NITROGEN
60101	1,514	WEBBING COTTON ALL TYPES
60103	1	ABLATIVE C/FIB FIBERITE MXC313
60104	713	LAMIN PHENOLIC/COTTON
60105	1	ABLATIVE COMPOUND PHENOLIC/SILICONE
60106		DELETED SEE 05824
60107	297	CARBON GRAPHITE BRUSH MATERIAL
60108	66	ADHESIVE CCX536/3561
60109		DELETED SEE 02343
60110	1,439	TAPE PAPER BACKED
60111	156	ADHESIVE EPOXYLITE 6001 COATING
60112	111	ADHESIVE ECCOBOND 60L
60113		DELETED SEE 06092
60114		DELETED SEE 62820
60115	382	COATING RESIN EPOXY
60116	151	ADHESIVE EPOXY LCA9/BA5
60117	1,244	POTTING COMPOUND ARCOSET 200 EPOXY
60118	232	ADHESIVE S2288
60119	1,264	PUTTY ZINC CHROMATE GENERAL PURPOSE
60120	69	ADHESIVE CHEMLOK 233
60121	1,396	SEALANT UF3195
60122	360	COATING LACQUER ACRYLIC
60123		DELETED SEE 20580
60124	751	LUBE O-RING
60126	1,331	RUBBER SILICONE CL 2A & 2B GR 70
60127	591	INK MARKING STENCIL
60128		DELETED SEE 60127
60129	751	LUBE MOS2 PETROLATUM
60130	1,271	RUBBER BUNA N
60131	568	GRAPHITE ATJ
60132	1,264	PROPELLANT LINER BSM U7L004B
60133	1,264	PROPELLANT BSM U7P19048
60134	544	FILM MYLAR PLASTIC 2 MIL
60135	463	FABRIC KEVLAR 49
60136	1,508	VELOSTAT 2.5 MIL
60137	1,072	PLASTIC POLYVINYL CHLORIDE (PVC)
60138	134	ADHESIVE EPON 825
60140	285	BEESWAX CB191

MATCD	PAGE	DESIGNATION
60141	81	ADHESIVE CREST 7450 POLYURETHANE
60142	629	INSULATION FOAM POLYISOCYANURATE XR1002
60143	645	INSULATION FOAM TEXTHANE 2000-24 ISOCYANAU
60144	574	HOSE FLUOROFLEX-T
60145	581	IGNTN GRANULES-BORON PTSM NITR
60146	591	INK MARKING PARACHUTES
60147	1,522	WEBBING TEXTILE ELASTIC COTTON
60148	337	COATING CORROSION INHIBITNG COMPOUND
60149	1,243	POLYETHYLENE
60150	745	LUBE GREASE KRYTOX 240AD
60151	10	ADHESIVE 583
60152	70	ADHESIVE CHEMLOK 608
60153	67	ADHESIVE CERAMIC TYCEMENT UF3242
60154	1,442	TAPE POLYURETHANE/ADHESIVE BACKNG 4000SE
60155	743	LUBE GREASE HD CALCIUM 2
60156	50	ADHESIVE BAP 1 PHENOL FORMALDEHYD
60157	174	ADHESIVE GRIP 10-115
60158	1,475	THREAD COTTON CORD ALL TYPES
60159	1,415	TAPE COTTON ALL TYPES
60160	1,522	WEBBING TEXTILE/NYLON/TUBULAR
60161	1,477	THREAD NYLON (ALL TYPES)
60162	500	FABRIC TEFLON
60163	448	FABRIC DUCK NYLON CLOTH
60164	419	CORD NYLON CORELESS
60165	528	FELT DACRON/POLYESTER/FIBREDYN
60166	627	INSULATION FOAM POLYETHYLENE FLEXIBLE
60167	1,520	WEBBING NYLON WOVEN
60168	253	ADHESIVE STABOND T161
60169	1,264	PUTTY ZINC CHROMATE 3992
60170	1,447	TAPE SCOTCH 471
60172	84	ADHESIVE DAP
60173	69	ADHESIVE CHEMLOK
60174	1,305	RUBBER NEOPRENE/SILICONE FILL
60176	388	COATING SS4171 SILANE
60177		DELETED SEE 06132
60178	1,309	RUBBER NYLON REINFORCED
60179	648	INSULATION FOAM URETHANE
60180	1,305	RUBBER NEOPRENE/CARBON FIBER
60181	132	ADHESIVE EPON 812
60182	1,317	RUBBER RTV 88
60183	157	ADHESIVE EPOXYLITE 8822
60184	432	EXPLOSIVE RDX/LSC
60185	1,450	TAPE SCOTCH 6 ACETATE
60189	126	ADHESIVE EPIBOND 156/956
60190	252	ADHESIVE SR529/SRC18
60191	1,262	POTTING COMPOUND SYLGARD 186
60192	628	INSULATION FOAM POLYISOCYANURATE 76-129
60193	581	INK 40M12864 BLACK
60194	1,439	TAPE PACKAGING VINYL WHITE
60195	40	ADHESIVE ARMSTRONG A12 EPOXY
60196	383	COATING RUBBER HYPALON NOC
60197	653	INSULATION MTA-1
60199	188	ADHESIVE M-BOND 600
60200	104	ADHESIVE EA946
60201	431	EXPLOSIVE HNS TYPE 1 GRADE A

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006705 0

MATCD	PAGE	DESIGNATION
60202	390	COATING TURCO T6109 WHITE
60203	1,250	POTTING COMPOUND EA937
60204	85	ADHESIVE DC282
60205	561	FLUX SOLDER
60206	1,346	RUBBER SILICONE RTV 3118
60208	431	EXPLOSIVE PETN
60209		DELETED SEE 06530
60210	416	CORD JET HMX AND RL-20-X
60211	1,339	RUBBER SILICONE NOC
60212	1,263	PROPELLANT
60213	378	COATING PRECUSSION
60214	1,264	PROPELLANT SOLID
60215	73	ADHESIVE CHOMERICS 360 EPOXY
60216	572	HEXANITRO STILBENE
60217	1,263	POWDER PROPELLANT GEN
60218	391	COATING TYSEAL 22W73 WHITE
60219	422	CORK COMPOUND K5NA
60220	393	COATING VINYL UTC4005-30301
60221	393	COATING VINYL UTC4005-30301 WHITE
60222	1,346	RUBBER SILICONE RTV 3120
60223		DELETED SEE 06382
60224	323	COATING ACRYLIC ENAMEL
60225	357	COATING HYPALON/GACOFLEX HFR2200
60226	422	CORK COMPOSITION
60227	654	INSULATION MTA-2
60228	188	ADHESIVE M-BOND 200
60229	357	COATING HYPALON/GACOFLEX H2200 WHITE
60230	653	INSULATION MSA-1
60231	756	LUBE SUPER-O-LUBE
60233		DELETED SEE 06177
60235		DELETED SEE 05066
60236	1,265	RDX
60237	565	GLASS PYREX
60238	714	LAMIN POLYESTER GLASS 181/150 HT
60239	615	INSULATION FOAM ECCOFOAM TYPE SH
60240	1,396	SEALANT UF3177
60241	1,396	SEALANT UF3119
60243	186	ADHESIVE LOCTITE 747-56
60244	1,250	POTTING COMPOUND EA919 UF3280 CORK
60246	448	FABRIC DUCK NYLON NATURAL
60247	311	COATING 443-3-17 BLACK EPOXY
60250	421	CORK B STAGE
60251	714	LAMIN PHENOLIC/S-GLASS CLOTH
60252	737	LUBE FLUOROGLIDE GRADE FB
60253	1,343	RUBBER SILICONE RTV 133
60254	714	LAMIN PLASTIC THERMOSETTING
60255	646	INSULATION FOAM TEXTHANE 333
60256	569	GREASE STERATE HYDROXYLIC CA12
60257	783	NYLON ORANGE
60259	359	COATING KRYLON RED-ORANGE
60260	576	HOSE NYLON COIL N344
60261	360	COATING LACQUER CELLULOSE NITRATE
60262	324	COATING ADHESIVE POLYSTYENE
60263	220	ADHESIVE POLYURETHANE MODIFIED STMM476
60264	3	ACRYLIC TRANSPARENT
60265	633	INSULATION FOAM POLYURETHANE OPEN CELL
60266		DELETED SEE 06212
60267	482	FABRIC NYLON FLAME RETARD
60268	1,479	THREAD POLYESTER F
60269	189	ADHESIVE M6704 EPOXY
60270	761	MICROFALLONS PHENOLIC
60272	223	ADHESIVE PR1590
60273	733	LUBE DRY NEDOX U4 FILM
60274	737	LUBE FLUOROGEL 865
60276	770	MOLD COMPOUND POLYESTER MICA FILLED
60277	249	ADHESIVE SILICONE GX6300
60278	1,352	RUBBER SILICONE RTV 652
60279	1	ABLATIVE MA255 T1
60280	707	LAMIN F161-1581/F50
60282	452	FABRIC FIBERGLASS/SILANE I399
60283	30	ADHESIVE AMSCO HOT MELT 344
60285	601	INSULATION BLASTAPE II G120 MX4702
60286	384	COATING S13-707 EPOXY
60287	531	FILLER MATERIAL ECCOSPHERES SI
60288	1,263	POWDER CAB-O-SIL M5
60289	154	ADHESIVE EPOXY RTC
60290	1,352	RUBBER SILICONE RTV 655
60291	297	CARBON BLACK
60292	341	COATING DC 92-046
60293	371	COATING POLYURETHANE 100 EPOXY WHITE
60294	371	COATING POLYURETHANE 710 EPOXY BLACK
60295	497	FABRIC SILICONE/NYLON H565
60296	686	LAMIN BALSA WOOD/ALUMINUM FACING
60297		DELETED SEE 20427
60298	490	FABRIC PHENOLIC/SILICA
60299	1,502	TUBING THERMOFIT 218 HST CONVLEX
60300	1,495	TUBING POLYOLEFIN HS FLAME RESISTANT
60301	1,486	TUBING FIBERGLASS SLV 1200
60303	1,243	POLYOLEFIN HS COMPONENTS
60304	231	ADHESIVE RUBBER NBR/MEK
60305	314	COATING 515X346 EPOXY
60306	617	INSULATION FOAM INSTA POLYURETHANE
60308	1,353	RUBBER SILICONE RTV 730
60309	344	COATING E28-4
60310	1,354	RUBBER SILICONE RTV 855
60311	1,264	PROPELLANT PELLET
60312	790	PAPER ONION SKIN
60313	359	COATING KRYLON LACQUER BLACK
60314	658	INSULATION THERMAL SILICA TAPE
60316	96	ADHESIVE DUCO
60317	51	ADHESIVE BONDING 6035
60318	748	LUBE GREASE SILICONE G683
60319	1,258	POTTING COMPOUND STYCAST 1467
60320	301	CERAMIC CEMENT PS-1032
60321	301	CERAMIC CEMENT PS-1027
60323	1,503	TUBING THERMOFIT S1017
60324	554	FILM TEMP SENSOR 110X
60325	623	INSULATION FOAM NOPCO H402-N-T/N-R
60326	1,413	TAPE BLASTAPE 2 STYLE MX4703
60328		DELETED SEE 60191

MSFC-HDBK-527 REV F 9999942 0006706 2

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
60331	727	LUBE DRY DRILUBE 842
60332	450	FABRIC FACILON NYLON/VINYL BLU
60333	736	LUBE ERNO FV0163015
60334	25	ADHESIVE AF126-2-03/06
60335		DELETED SEE 61314
60336	26	ADHESIVE AF3015
60337	313	COATING 463-7-26/A276/X-369
60338	467	FABRIC NARMCO 506 GLASS PHENOL
60339	197	ADHESIVE METLBOND 1133 FOAM
60340	143	ADHESIVE EPOTEK 353 EPOXY
60341	148	ADHESIVE EPOWELD 8173
60342	1,250	POTTING COMPOUND DC183
60343	560	FLUX
60344	1,250	POTTING COMPOUND DC7521 SILICONE
60345	1,444	TAPE SCOTCH 1157
60346	599	INSULATION 60
60347	731	LUBE DRY MOLYKOTE 3
60348		DELETED SEE 05624
60350	337	COATING CORR RES KORROSION SHULTZ
60351	72	ADHESIVE CHOBOND 320
60352	330	COATING CHEMGLAZE 9922 A/B
60353	177	ADHESIVE ISOTAC ACRYLIC
60354	124	ADHESIVE EPIBOND 1210/9615A EPOXY
60355	85	ADHESIVE DC6-1004
60356	322	COATING ACCUMETRIC A105
60357	151	ADHESIVE EPOXY FM73M FILM ON POLYESTER MAT
60358	182	ADHESIVE LEKUTHERM X227
60359	58	ADHESIVE BSL 312
60360	327	COATING BSL 112 PRIMER
60361	253	ADHESIVE STRUCOL R1610
60362	253	ADHESIVE STRUCOL R1612
60363	36	ADHESIVE ARALDITE 138/HV998
60364	620	INSULATION FOAM MISSELON POLYETHER
60365	198	ADHESIVE METLBOND 306/112 FOAM
60367	58	ADHESIVE BSL 319
60368	58	ADHESIVE BSL 119 PRIMER
60369	43	ADHESIVE ARMSTRONG C1 EPOXY
60370	1,432	TAPE MYSTIK 7452 ALUMINUM/ACRYLIC ADHESIVE
60371	1,422	TAPE G408862 ALUMINUM/KAPTON/ADHESIVE
60372	1,422	TAPE G408460 THICK BLACK FILM WITH .5 MIL KAPTON AND 1 MIL SILICONE ADHESIVE
60373	1,445	TAPE SCOTCH 346 DOUBLE COAT PS
60374	737	LUBE FILM SOLID
60375	1,470	TEFLON TFE FILLED NOC
60376	1,424	TAPE GLASS/THERMOSET PS
60377	592	INK NOC
60378	280	AMCERMET 701-N65
60379		DELETED SEE 20017
60380		DELETED SEE 20259
60381	1,429	TAPE MX4703-2
60382	52	ADHESIVE BOSTIK 1008
60383	1,395	SEALANT TORQUE F900
60384	1,354	RUBBER SILICONE RTV DC3-6077
60385	66	ADHESIVE CEMABOND 571
60386	601	INSULATION CEMA FIBER 111
60387	431	ETCHANT-BONDAIV S16943
60388	1,347	RUBBER SILICONE RTV 345
60389	617	INSULATION FOAM INSTA KIT 115
60391	652	INSULATION JS220
60392		DELETED SEE 60310
60393	1,392	SEALANT PROSEAL 870
60394	1,427	TAPE LOOP
60395	1,412	TAPE 898
60398	722	LINE LACING G-1008
60399		DELETED SEE 60380
60400	503	FABROID T1 GLASS/TEFLON 50/50
60401	1,424	TAPE JACKET 602-35-7010
60402	232	ADHESIVE S1017
60403		DELETED SEE 05328
60404	280	AHH 847
60405	416	CORD FIBERGLASS
60406	99	ADHESIVE EA1347
60407	568	GREASE 880C & C
60408	420	CORD SF2600
60409	737	LUBE FELPRO C100
60410	1,467	TAPE WOVEN
60411	99	ADHESIVE EA815
60412	1,536	XR-5236
60413	362	COATING M COAT
60414	150	ADHESIVE EPOXY 907
60415	188	ADHESIVE M-BOND
60416		DELETED SEE 20455
60417	280	ARCOSET
60418	1,243	POLYURETHANE
60420	400	COMPOUND JACKET
60422	1,242	POLY (AMIDE-IMIDE)
60423	1,289	RUBBER FLUOREL FC2174
60424	372	COATING POLYURETHANE LACK181/3
60425	114	ADHESIVE ECCOSIL 4952/50
60426	380	COATING PTFE DISPERSION
60427	792	PASTE 97% GOLD ELECTRICAL COND
60428	38	ADHESIVE ARALDITE AV100
60429	1,448	TAPE SCOTCH 5 POLYESTER
60430	113	ADHESIVE ECCOFOAM EFF14
60431	285	BEADS GLASS SODALIME TY SILICA
60433	381	COATING PYROLAC P123
60434	1,243	POLYIMIDE-CU
60435	1,527	WIRE ELEC LACKDRAHTW180HW11
60436	762	MOLD COMPOUND C2175 EPOXY
60437	340	COATING DC 1201 CLEAR SILICONE
60438	208	ADHESIVE P75 FOAM
60439	673	LACING TAPE DACRON
60440		DELETED SEE 05084
60441	1,431	TAPE MYSTIK 7321 MYLAR/SILICONE
60442		DELETED SEE 05005
60443	695	LAMIN EPOXY/GLASS E747/VOLAN/1581
60444	285	BLADDER BUTYL RUBBER
60445	410	CONNECTOR ELECTRICAL 22541
60446	401	COMPOUND THERMACOTE BLUE POLYBUTENE
60447	526	FASTENER VELCRO POLYESTER LOOP 2000 BACKING 1299

MSFC-HDBK-527 REV F 9999942 0006707 4

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
60448	361	COATING LATEX 4699-126
60449	199	ADHESIVE MINCO 21365/7-1
60450	513	FASTENER VELCRO NOMEX LOOP 2000 BACKING 0399
60451	625	INSULATION FOAM PDL4034/COATED WITH FRL
60452	663	KEL-F PLASTICIZED
60453	465	FABRIC KYNOL
60454	781	MULTI-LAYERED INSULATION VT70-060065 AL/POLYIMIDE
60455	1,478	THREAD NYLON VT295 SIZE E
60456	513	FASTENER VELCRO NOMEX LOOP 2000 BACKING 2699
60457	519	FASTENER VELCRO NYLON HOOK AND LOOP WITH FR127A ADHESIVE
60458	523	FASTENER VELCRO NYLON LOOP WITH FR127 ADHESIVE
60459	510	FASTENER VELCRO HOOK 80 BACKING 2899
60460	510	FASTENER VELCRO HOOK 80 BACKING 2699
60461	510	FASTENER VELCRO HOOK 80 BACKING 9999
60462	514	FASTENER VELCRO NOMEX LOOP 2000 BACKING 9999
60463	523	FASTENER VELCRO POLYESTER HOOK 80 BACKING 0199
60464	510	FASTENER VELCRO HOOK 80 BACKING 0399
60465	510	FASTENER VELCRO HOOK 80 BACKING 1299
60466	513	FASTENER VELCRO NOMEX LOOP 2000 BACKING 1299
60467	1,462	TAPE TEFLON PTFE ANTISEIZE
60468	1,521	WEBBING NYLON/NEOPRENE 3090
60469	510	FASTENER VELCRO HOOK AND LOOP 100 BACKING 3099AB
60470	674	LACING TAPE GORTEX
60471	739	LUBE GREASE BRAYCO NPT4
60472	1,515	WEBBING DACRON 800 LB
60473	515	FASTENER VELCRO NYLON HOOK 65 BACKING 2699
60474	1,338	RUBBER SILICONE MEDICAL GRADE
60475	785	PANEL HONEYCOMB/COATING CTL 15
60476	1,452	TAPE SCOTCH 800 TEFLON PRESCRIPTION
60477	1,340	RUBBER SILICONE PARCO 1235-70
60478	164	ADHESIVE FILM CMC122
60479	1,526	WIRE ELEC KAPTON FEP POLYIMIDE
60480	656	INSULATION SILFRAY CERAMIC
60481	436	FABRIC ANCHORAGE 2
60482	681	LACING TAPE PBI/VITON 1330
60483	280	ANTI-PERSPIRANT DIAL UNSCENTED
60484	368	COATING PENNWALT 4699-122-A
60485	368	COATING PENNWALT 4699-121-A
60486	1,303	RUBBER NEOPRENE NS107
60487	711	LAMIN HONEYCOMB LEASAT ANTENNA
60488	462	FABRIC KELVAR 29
60489	705	LAMIN EPOXY/KEVLAR CE342
60490	533	FILM CMC122 KAPTON ADHESIVE COATED
60491	1,429	TAPE MYLAR 49/SILICONE
60492	791	PAPER STICKY-BACK WHITE
60493	386	COATING SILICONE VESTAR Q9-6503
60494	1,412	TAPE ACETATE/LEXAN TP1-31
60495	665	LABEL 7720/7710/7920/ADHESIVE 400
60496	752	LUBE OIL FOMBLIN Y16
60497	1,502	TUBING THERMOFIT RT218
60498	749	LUBE GREASE SUPERMIL ASU31052
60499		DELETED SEE 06374
60501	1,461	TAPE TA44-2
60502	353	COATING GLYPTAL 1201 RED
60503	1,474	TERMINAL LUG
60504	680	LACING TAPE NYLON
60505		DELETED SEE 05275
60506	203	ADHESIVE N136
60507	348	COATING EPOXY CF32A806
60508	725	LUBE DRY DAG 213 DISPERSION
60509		DELETED SEE 20452
60510	726	LUBE DRY DAG 217 DISPERSION
60511	1,318	RUBBER SILASTIC 735
60512	1,340	RUBBER SILICONE R425
60513	547	FILM PHOTOGRAPHIC
60514		DELETED SEE 05449
60515	241	ADHESIVE SCOTCHWELD EC588
60518	638	INSULATION FOAM PYRELL/PRESTO P/6
60519	419	CORD PBI STYLE S121
60520		DELETED SEE 06170
60521	1,357	RUBBER SILICONE S59
60522	673	LACING TAPE FIBERGLAS 50LOF13X
60523	229	ADHESIVE RELIABOND 7115 EPOXYFILM
60524	749	LUBE GREASE THERMOCOTE 250
60525	566	GLOVE COMFORT COTTON/POLYESTER
60586	1,337	RUBBER SILICONE K1203
60587	44	ADHESIVE ARMSTRONG C2/A EPOXY
60588	385	COATING SF-X-HARDCOAT ANTISCRATCH
60589	385	COATING SHC1200 HARDCOAT
60590	1,446	TAPE SCOTCH 444 POLYESTER DOUBLE BACK
60591	793	PEN CROSS 3504/REFILL 8543
60592	1,458	TAPE SCOTCHCAL 8015
60596	1,455	TAPE SCOTCH Y9469 ACRYLIC TRANSFER
60597	794	PEN PENTEL S520 BLUE
60598	794	PEN PENTEL S520 GREEN
60599	794	PEN PENTEL S520 BLACK
60600	535	FILM EKTACHROME VIDEO TY 4250
60601	1,503	TUBING TYGON S54HL
60602	1,499	TUBING SILICONE MS50G38
60603	523	FASTENER VELCRO POLYESTER HOOK 80 BACKING FR8299
60604	654	INSULATION POLYESTER FIBERMAT 2538
60605	1,336	RUBBER SILICONE GROENDYK 7504
60606	1,540	ZIPPER NYLON/POLYESTER WHITE
60607	441	FABRIC COTTON CHEESE CLOTH
60608	250	ADHESIVE SILVERBOND CONDUCTIVE
60609	1,495	TUBING POLYOLEFIN GPO135 BLK
60610	1,460	TAPE STRETCH RL6000SA
60611	310	COATING 44 GM-7 AIRCRAFT
60612	1,499	TUBING SILICONE RX50 SILASTIC
60613		DELETED SEE 20755
60614	1,393	SEALANT SILICONE HIGH VACUUM
60615	487	FABRIC PANOTEX GRAY P-32
60616	1,336	RUBBER SILICONE FMS510
60617	491	FABRIC POLYESTER STYLE 15458
60618	791	PAPER TYVEK
60619	1,520	WEBBING NYLON P8229
60620	1,332	RUBBER SILICONE CP6007
60621	430	ENVEX 100 POLYIMIDE
60622	606	INSULATION FOAM CHEMLON 103

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
60623	606	INSULATION FOAM CHEMLON 403
60624	1,449	TAPE SCOTCH 567
60625	641	INSULATION FOAM SCOTT S150-50 GRAY
60626	481	FABRIC NYLON A5691
60627	564	GEL ELECTRODE DERMA-JEL
60628	740	LUBE GREASE BRAYCOTE 601
60629	439	FABRIC COTTON 100% COMFORT 3640
60630	607	INSULATION FOAM CONFOR C40
60631	608	INSULATION FOAM CONFOR C47
60632	607	INSULATION FOAM CONFOR C45
60633	679	LACING TAPE NOMEX/VITON 1342VC
60634	607	INSULATION FOAM CHEMLON 503
60635	1,497	TUBING POLYOLEFIN RTA125 HST
60636	1,494	TUBING POLYOLEFIN DWP125
60637	1,489	TUBING INSULTITE VFP876 HST BLACK
60638	1,459	TAPE SCOTCHMOUNT 4408
60639	613	INSULATION FOAM CREST 3030 TAN
60640	613	INSULATION FOAM CREST 7530 TAN
60641	248	ADHESIVE SILGRIP SR6573 SILICONE
60642	754	LUBE OIL HALOCARBON SERIES 27S
60643	1,381	RUBBER VITON V747-75
60644		DELETED SEE 06623
60645		DELETED SEE 20455
60646	176	ADHESIVE IBM240
60647	1,540	ZIPPER NYLON CHAIN 10VF
60648	774	MOTOR GLOBE
60649	659	INSULATION WIRE ESTANE 58202
60650	1,524	WIRE ELEC ESTANE 58300
60651	1,533	WIRE ELEC TRIAXIAL
60652	1,403	SPONGE ESTER POLYURETHANE
60653	1,443	TAPE RETROREFLECTIVE 3870
60655	407	CONNECTOR ELEC M1KM0-1-7-SH016
60656	407	CONNECTOR ELEC M1K6-1-7-PH016
60657	407	CONNECTOR ELEC DDM43W2SK52
60658	1,539	ZIPPER BRASS/NYLON/MYLAR
60659	419	CORD POLYESTER
60660	405	CONNECTOR 40M RECEPTACLE/PLUG
60661	832	PLASTIC BN101 ACRYLIC PVC
60662	361	COATING LATEX 1500 FLAMEREST
60663	1,447	TAPE SCOTCH 468
60664	793	PEN BIC F39 BLACK
60665	395	COATING XYLAN 1010 BLACK
60666	770	MOLD COMPOUND PLENCO 1512 ALKYD/GL
60667	1,464	TAPE TEMP-R-TAPE HM350 TFE/SIL
60668	1,475	THREAD DACRON "E"
60669	1,519	WEBBING NYLON 400 LB
60670	1,519	WEBBING NYLON 750 LB
60671	498	FABRIC STYLE 5035 FINISH 8362
60672	154	ADHESIVE EPOXY R313
60673	703	LAMIN EPOXY/GRAPHITE GY70/X30
60674	516	FASTENER VELCRO NYLON HOOK 65 BACKING FR8299
60675		DELETED SEE 06614
60676	490	FABRIC POLYESTER E-1438
60677	1,414	TAPE CASSETTE
60678	780	MULTI-LAYERED INSULATION POLYURETHANE FOAM 416/ SUPER KOROPON/RTV 560/HYPALON
60679	314	COATING 528-305/515-700 PRIMER
60680	317	COATING 821-331 POLYURETHANE FLAT WHITE WITH PRIMER
60681		DELETED SEE 60680
60682	762	MINISWITCHES
60683	721	LED DISPLAY
60685	209	ADHESIVE PERMABOND 200
60686	1,369	RUBBER VITON 133 ELASTOMER
60687	281	ARMALON TG 4140
60688	67	ADHESIVE CERAMIC ULTRATEMP 516
60689	685	LAMIN ASBESTOS/FIBERGLASS RVV647F
60690	279	ADHESIVE XR5038 EPOXY
60691	1,243	POLYCAST RG256-57-3
60692		DELETED SEE 60974
60693	213	ADHESIVE PLASTILOCK 729-3/728
60694	361	COATING LATEX 4367-3 UNPIGMENTED
60695	606	INSULATION FOAM CHEMLON 203
60697		DELETED SEE 62329
60698	1,404	SPONGE FLUOREL RL 4714
60699	1,412	TAPE 58
60700	787	PAPER ESP-14
60701	1,265	RECORDER AUDIO 2625
60702	286	BLOWER BRAILSFORD MODEL TB1-1
60703	1,243	POTENTIOMETER TYS
60704	408	CONNECTOR ELECTRICAL
60705	410	CONNECTOR ELECTRICAL 73E
60706	416	CORD ELASTIC RUBBER/KEVLAR/COTTON
60707	382	COATING RC9108 EPOXY
60708	359	COATING KRYLON 150 CRYSTAL WHITE
60709	475	FABRIC NOMEX S470/ZEPEL 86900
60710	1,531	WIRE ELEC RAYCHEM 44 MYLAR/KAPTON
60711	602	INSULATION FIBERMAT 2539
60712	773	MOLD COMPOUND RYTON R-6
60713	107	ADHESIVE EC3549 A/B POLYURETHANE
60714	326	COATING BARRY CONTROLS 103
60716	421	CORK B-380FA
60717	383	COATING RUSTOLEUM 760
60718	268	ADHESIVE UNISET A451 EPOXY
60719	236	ADHESIVE SCOTCHGRIP 2126
60720	756	LUBE SANDSTROM 9A
60721	236	ADHESIVE SCOTCHGRIP 1099 VINYL
60722	1,466	TAPE VIDEO 400 BLACK
60723	204	ADHESIVE NEOPRENE E2084
60724	427	DRIVER IMPACT PIT-120
60725	532	FILM ACLAR 22A
60726	324	COATING ACRYLIC PC20/20M
60727		DELETED SEE 60726
60728	579	HOSE TEFLON PTFE R765
60729	1,483	TUBING BEN-HAR EXPANDO
60730	1,355	RUBBER SILICONE RTV R2501
60731	131	ADHESIVE EPON 1001F/VERSAMID 115
60732	560	FLUX HANDY TYPE B-1
60733	1,464	TAPE TEMP-R-TAPE HM50

MSFC-HDBK-527 REV F 9999942 0006709 8

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
60734	595	INK STENCIL BLACK
60735	749	LUBE GREASE THERMAL JOINT CPD
60736	312	COATING 463-3-33 TC/515-700 PRIMER
60737	660	KEL-F 6060
60738		DELETED SEE 05521
60739	753	LUBE OIL HALOCARBON 80-114
60740	693	LAMIN EPOXY/GLASS CE9020/7781
60741	432	EYE PENCIL ALMAY COLOR GENTLE
60742	762	MINISWITCH N7-L-438
60743	432	EYE COLOR FROST FORMULA 2
60744	567	GLOVE RUBBER E-091 VITON
60745	3	ACOUSTA STYLE 200
60746	1,265	RAZOR NORELCO ROTARY WITH CHARGER
60748	297	CAN RODENT
60749	567	GLOVE VINYL DISPOSABLE 25165
60750	645	INSULATION FOAM TEMPERFOAM C42
60751	961	PLASTIC LEXAN ZELUX M GLASS FILLED
60752	414	COOLANT FC-40
60753	789	PAPER MAPS JCP E-20
60754	359	COATING KRYLON 1602
60755	532	FILM ACLAR 2100
60756	627	INSULATION FOAM POLYETHER/POLYURETHANE OPEN CELL
60757	415	CORD DACRON 1101 P2
60758	511	FASTENER VELCRO NOMEX HAQ 12-2 LOOP WITH 6-1015 NEOPRENE ADHESIVE
60759	535	FILM CUPRON PMPX-C .0002"
60760	540	FILM KODAK 160 COLOR MOVIE
60761	619	INSULATION FOAM MINICELL L200 FR
60762	430	EMBLEM CLOTH SHUTTLE
60763	635	INSULATION FOAM POLYURETHANE/TAPE AL 425
60764	103	ADHESIVE EA9414 EPOXY
60765	626	INSULATION FOAM POLYETHER C190-39 GREEN
60766	314	COATING 5205U PAINT WITH 8248 PRIMER
60767	315	COATING 6561U PAINT WITH EPOXY PRIMER
60768	113	ADHESIVE ECCOBOND SOLDER V91
60769	1,250	POTTING COMPOUND ECN1235/ALUMINUM-OXIDE F
60770	1,244	POTTING COMPOUND 93-500/CU MICROSPHER
60771	1,244	POTTING COMPOUND 93-500/ALUMINUM-OXIDE FILL
60772	24	ADHESIVE ADIPRENE L100/ALUMINUM OXIDE
60773		DELETED SEE 05609
60774		DELETED SEE 60728
60775	513	FASTENER VELCRO NOMEX LOOP 0.75 INCH
60776	593	INK PILOT FINELINER SWPP GREEN
60777	593	INK PILOT FINELINER SWPP BLUE
60778	593	INK PILOT FINELINER SWPP BLACK
60779		DELETED SEE 60484
60780	776	MULTI-LAYERED INSULATION ALUMINIZED KAPTON/ ALUMINIZED MYLAR/DACRON/NOMEX
60781	675	LACING TAPE GUDETEMP 723G NOMX
60782	1,358	RUBBER SILICONE S64
60783	1,358	RUBBER SILICONE S66
60784	778	MULTI-LAYERED INSULATION HITCO TG15000/G134600 GOLDIZED KAPTON
60785	467	FABRIC NETTING/POLYPROPYLENE
60786	298	CELCON M-90-24 ACETAL POLYMER
60787	1,522	WEBBING TY WD901
60788	440	FABRIC COTTON 591 FLOCK
60789	672	LACING TAPE 615-158-3
60790	672	LACING TAPE 615-158-5
60791	672	LACING TAPE 615-158-1
60792	779	MULTI-LAYERED INSULATION KAPTON/MYLAR/DACRON NET
60793	1,516	WEBBING KEVLAR FRL-S201
60794	77	ADHESIVE CONBOND CONTACT CEMENT
60795	51	ADHESIVE BONDMASTER G781
60796	626	INSULATION FOAM POLYCARBODIMIDE
60797	187	ADHESIVE LOCTITE LO555
60798	572	HELMET FLIGHT ANTI-G
60799		DELETED SEE 06146
60800	185	ADHESIVE LOCTITE 601 EPOXY
60801	687	LAMIN DECLAD 810 COPPER COATING
60802	551	FILM SARAN 18L
60803		DELETED SEE 60792
60804		DELETED SEE 60784
60805	10	ADHESIVE 76/URETHANE FOAM
60806	592	INK PEN ACCUTEC
60807	383	COATING RK692
60808	541	FILM LMC300 KAPTON
60809	187	ADHESIVE LOCTITE HV
60810		DELETED SEE 06644
60811	781	NALGENE MA 255 TYPE 4
60813	761	MICROPHONE PREAMP 1400
60815	746	LUBE GREASE OXY 8
60816	753	LUBE OIL HALOCARBON 11-21S
60817	756	LUBE PARKER O-LUBE SILICONE
60818	574	HOSE FLEX TURBOFAB FLUOROSILICONE
60819		DELETED SEE 20768
60821	574	HOSE FLEX SILFAB-2 SIL/GL/FAB
60822	574	HOSE FLEX SILFAB-1 SIL/GL/FAB
60823	778	MULTI-LAYERED INSULATION GOLDIZED KAPTON/DACRON MESH/NOMEX
60824	1,387	SEALANT DUXSEAL
60825	787	PAPER ELECTROGRAPHIC 45R11
60826	1,429	TAPE MYLAR ALUMINIZED
60827	730	LUBE DRY LUBRIBOND 320
60828	720	LEAD TAXCHEM MARKING 200 BLUE
60832	593	INK PILOT FINELINER SWPP RED
60833	573	HOSE ASSEMBLY TITEFLEX R270-4
60834	754	LUBE OIL HOUGHTO-SAFE 1055
60835	754	LUBE OIL HOUGHTO-SAFE 1120
60836	673	LACING TAPE FRL 615-158 PBI
60837	673	LACING TAPE FRL 615-157 PBI
60838	366	COATING PARYLENE D
60839	73	ADHESIVE CMC634-2
60840	611	INSULATION FOAM CPR9545 POLYISOCYANURATE
60841	1,476	THREAD KEVLAR B66
60842		DELETED SEE 60792
60843	26	ADHESIVE AF770
60844	1,496	TUBING POLYOLEFIN RT301/S1024
60845	73	ADHESIVE CMC19-2
60846	111	ADHESIVE ECCOBOND 56/C11

MSFC-HDBK-527 REV F 9999942 0006710 4
Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
60847	1,332	RUBBER SILICONE CL 3B GR 30
60848	1,336	RUBBER SILICONE HADBAR 3250
60849	1,336	RUBBER SILICONE HADBAR 3254
60850	1,337	RUBBER SILICONE HERCULES H564
60851	1,332	RUBBER SILICONE CL 3A GR 25
60852	1,336	RUBBER SILICONE H567
60853	463	FABRIC KEVLAR 343
60854	575	HOSE FLUOROFLEX-T T1000
60855	676	LACING TAPE HT-30 SPACE.5 INCH
60856	775	MOTOR P/N47A232920A S/N02
60857	409	CONNECTOR ELECTRICAL
60858	265	ADHESIVE TRABOND BB2116
60859	1,470	TEFLON RING PISTON RIDER
60860	677	LACING TAPE NOMEX 1251P
60861	681	LACING TAPE PBI/VITON 1330VC
60862	749	LUBE GREASE TRIBOLUBE 10C
60863	516	FASTENER VELCRO NYLON HOOK 65 BACKING PS 0107
60864	517	FASTENER VELCRO NYLON HOOK 65 WITH PS 0104 ADHESIVE
60865	732	LUBE DRY MOLYKOTE 3402 MOS2
60866	676	LACING TAPE HT-30 SPACE 1 INCH
60867	679	LACING TAPE NOMEX/VITON 1342V
60868	1,536	YARN 200-100-R79-430 NOMEX
60869	676	LACING TAPE HT-30 NOMEX
60870	526	FASTENER VELCRO POLYESTER LOOP 2000 WITH Y966 TAPE
60871	447	FABRIC DELNET R0709 POLYPROPYL
60872	489	FABRIC PHENOLIC/CARBON FM5055G
60873	767	MOLD COMPOUND FIBERITE FM4008
60874	401	COMPOUND THERMACOTE NOC SILICONE
60875	1,404	SPONGE FLUOROELASTOMER R1M693
60876	344	COATING E85552 RESIN WHITE EPOXY
60877		DELETED SEE 60726
60878	521	FASTENER VELCRO NYLON LOOP 1000 WITH PS 0104 ADHESIVE
60879	511	FASTENER VELCRO NOMEX HAQ 12-1 HOOK WITH 6-1015 NEOPRENE ADHESIVE
60880		DELETED SEE 05658
60881	468	FABRIC NOMEX 2PLY/FELT-1PLY
60882	468	FABRIC NOMEX 2PLY
60883	361	COATING LATEX 4699-121B
60884	521	FASTENER VELCRO NYLON LOOP 1000 BACKING PS 0107
60885	1,422	TAPE G407925 PS ADHESIVE
60886	1,313	RUBBER POLYPHOSPHAZENE (PNF)
60887	1,398	SHIELD RADIATION
60888	1,266	RELEASE AGENT X-AIR 4N002
60889		DELETED SEE 20620
60890	570	HANDLE DRIVER F40A
60891	570	HANDLE DRIVER F50
60894	501	FABRIC TREVIRA POLYEST 207 GRN
60895		DELETED SEE 61407
60896	518	FASTENER VELCRO NYLON HOOK 65 WITH PS 0140 ADHESIVE
60897	572	HEATER WATLOW 02205580
60898	758	MARKER METALLIC NIJI GREEN
60899	758	MARKER METALLIC NIJI WHITE
60900	433	EYE SHADOW PENCIL MAXI-SOFT
60901	432	EYE SHADOW #35-4.023-4091
60902	1,488	TUBING FRC125 HST
60903	793	PEN EXPRESSO 2901/2902N RED
60904	664	KEYBOARD COMPUTERWISE TT1A
60905	1,410	STRAP EYEGLASS RETENTION
60906	519	FASTENER VELCRO NYLON HOOK AND LOOP 80 BACKING PS 0172
60907	394	COATING WATER-ACRYLIC ENAMEL BLUE
60909	432	EYE COLOR STICK PROFESSIONAL
60911	518	FASTENER VELCRO NYLON HOOK 80 WITH PS 0172
60912	1,399	SHOE POLISH KIWI BROWN
60913	730	LUBE DRY LUBRIBOND 220 FILM
60914	1,477	THREAD NOMEX SILICONE FINISH
60918	643	INSULATION FOAM STEPAN BX352M/OCEAN CM987
60919	3	ABSORBER SOUND GP-2 DAMPING
60921	1,524	WIRE ELEC ESTANE 58866 INSUL
60923	1,481	TONOMETER INTRAOCULAR PRESSURE
60924	1,370	RUBBER VITON 2702-75
60925	1,265	RECORDER STRIP CHART/THERMAL/2 CHANNEL
60926	1,464	TAPE TEMP-R-TAPE HM430
60927	956	PLASTIC LEXAN 9030 POLYCARBONATE
60929	511	FASTENER VELCRO LOOP NYLON 80 WITH PS 0172
60930	1,324	RUBBER SILICONE 11307
60931		DELETED SEE 05276
60932	649	INSULATION FOAM URETHANE R248E
60933	642	INSULATION FOAM SLATHANE 821-10
60934	453	FABRIC FLANNEL VIRGIN
60935	429	EARSEAL 61B883 URETHANE/FLOURL
60937	682	LACING TAPE PYROLACE HT 30LOCC
60938	345	COATING ENAMEL A316/A136 EXP PRIMER
60939	522	FASTENER VELCRO NYLON LOOP 200 BACKING 0199
60940	494	FABRIC RYTON
60941	347	COATING EPICEL 3 EPOXY/CURE AGENT U
60942	128	ADHESIVE EPISEAL 20-20 EPOXY
60943	514	FASTENER VELCRO NOMEX LOOP FR 0327 PRECOAT
60944	676	LACING TAPE HT-30-LOC A ORANGE
60945	439	FABRIC COTTON 100%(FR/2%THPOH)
60946	477	FABRIC NOMEX TWILL 98379 6 OZ.
60947	449	FABRIC DURETTE HCO-2
60948	632	INSULATION FOAM POLYURETHANE HR28
60949	542	FILM MYLAR 305 YELLOW/JCP E20
60950	542	FILM MYLAR 105 CLEAR/JCP E20
60951	543	FILM MYLAR 915 BROWN/JCP E20
60952	493	FABRIC RAYON/NOMEX
60953	494	FABRIC RAYON/WOOL
60954	620	INSULATION FOAM MINICELL L200/FREKOTE COATED
60955	1,495	TUBING POLYOLEFIN HST THERMAPOD
60956	702	LAMIN EPOXY/GRAPHITE 3501/AS
60957	500	FABRIC TEFLON T162
60958		DELETED SEE 05513
60959	706	LAMIN EPOXY/KEVLAR F164/120 KEVLAR 49
60960	379	COATING PROTEXOCOTE M70
60961	488	FABRIC PBI FRL-73300-190 FX
60962	702	LAMIN EPOXY/GRAPHITE 5208/T300

MSFC-HDBK-527 REV F ■ 9999942 0006711 6 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
60963	514	FASTENER VELCRO NOMEX LOOP 2000 BACKING 2899
60964	704	LAMIN EPOXY/GRAPHITE HMF330B/34
60965	521	FASTENER VELCRO NYLON LOOP 1000 FR 8299
60966	790	PAPER PHOTO CIBACROME
60967	547	FILM PHOTO LP4
60968	547	FILM PHOTO LP7
60969	546	FILM PHOTO EN7
60970	790	PAPER PHOTO 74 RC EKTACOLOR
60971	520	FASTENER VELCRO NYLON HOOK NOMEX GROUND TAPE WITH FR 0327 PRECOAT
60972	512	FASTENER VELCRO NOMEX HI-AIR LOOP 2000 BACKING 0199W
60973	508	FASTENER VECRO HI-AIR NYLON HOOK 65 WITH NOMEX GROUND
60974	322	COATING A1716/BT1-1
60975	105	ADHESIVE EC1022
60976	520	FASTENER VELCRO NYLON LOOP 100 BACKING 0199
60977	571	HEATER BELT AV14493
60978	1,251	POTTING COMPOUND EPOXY 0-73027-1
60979	258	ADHESIVE THERMOFOAM 3008
60980	730	LUBE DRY LUBELOK 66C FILM
60981	709	LAMIN G7-832
60982	491	FABRIC POLYESTER STYLE67004/08
60983	338	COATING D65/TOPCOAT 904
60984	554	FILM TUFTANE T310 POLYURETHANE
60985	525	FASTENER VELCRO POLYESTER HOOK 80 WITH Y966 TAPE
60986	267	ADHESIVE UK8202/UK5400
60987	579	HOSE TEFLON PTFE R735
60989	481	FABRIC NYLON A2598/15 LT BLUE
60990	686	LAMIN CLEER-ADHERE 65001
60991	396	COMB STYLING MARK IV
60992	144	ADHESIVE EPOTEK 877
60993	16	ADHESIVE ABLEBOND 185 EPOXY
60994	312	COATING 463-12-8/643-2-20 EPOXY
60995	669	LABEL LETRALINE #11
60996	576	HOSE NEOPRENE P/N 801005
60997	557	FLASHLIGHT STREAMLITE 15
60998	1,429	TAPE MYLAR INS102 ALUMINIZED
60999	527	FASTENER VELCRO VELCOIN 1000 PS 0107
61000	155	ADHESIVE EPOXY V5H734R24
61001	157	ADHESIVE EPOXYLITE 8751
61002	1,256	POTTING COMPOUND SCOTCHCAST 8/DC3140
61003	1,406	SPONGE RUBBER NEOPRENE R425N
61004	349	COATING EPOXY PRIMER A136-2CP AB
61005	557	FLASHLIGHT STREAMLITE 20
61006	327	COATING BROMA 101 CLEAR ACRYLIC
61007	585	INK CAT-L-INK 50-770
61008	488	FABRIC PBI FRL-73300-196 FX
61009	606	INSULATION FOAM CHEMLON 200 FF NRL25
61010	606	INSULATION FOAM CHEMLON 100TA PC
61011	1,415	TAPE CHARTPAK GRAPHIC 5014 PS BROWN
61012	567	GLOVE VINYL DERMA THIN
61013	484	FABRIC NYLON/COTTON RES JACKET
61014	595	INK SERIES 3900 HT9040
61015	493	FABRIC POPLIN NOMEX
61016	385	COATING SILICONE BLACK VHT SP102
61017	257	ADHESIVE TERLAN 1580 POLYIMIDE
61018	1,456	TAPE SCOTCH Y9473 TRANSFER
61019	1,455	TAPE SCOTCH Y9460 TRANSFER
61020		DELETED SEE 05296
61021	430	ENVEX 1115 POLYIMIDE
61022	501	FABRIC TWILL EX 3A 1.93 6.9 OZ
61023	495	FABRIC SATEEN EX 1B HC 6.9 OZ
61024	749	LUBE GREASE TRIBOLUBE 10
61025	1,538	ZIPPER 32" 5283-021B-4A40-0030
61027	645	INSULATION FOAM TENNECO 6LBN BLACK
61029	1,371	RUBBER VITON 871
61030	664	KNEEBOARD ASSEMBLY WITH MECHANICAL PENCIL
61031	579	HOSE TEFLON T6C
61032	652	INSULATION GLASS/SILICONE M-S-AA
61033	410	CONNECTOR ELECTRICAL 18-32P #1
61034	410	CONNECTOR ELECTRICAL 18-32 #4
61035	134	ADHESIVE EPON 8201/CAT Z/HMS FIBE
61036	518	FASTENER VELCRO NYLON HOOK 65 WITH PS 0172 ADHESIVE
61037	522	FASTENER VELCRO NYLON LOOP 1000 WITH PS 0172 ADHESIVE
61038	12	ADHESIVE A1282B EPOXY
61039	518	FASTENER VELCRO NYLON HOOK 80 BACKING 0199W
61040	525	FASTENER VELCRO POLYESTER LOOP 1000 FR PS 8222
61041	525	FASTENER VELCRO POLYESTER HOOK 80 WITH FR PS 8222
61042	298	CARDS CUE PAPER
61043	286	BLADES RAZOR SCHICK SUPER II
61044		DELETED SEE 60863
61045	521	FASTENER VELCRO NYLON LOOP 1000 PS 0100
61046	498	FABRIC SUPERTWILL 48 COTTON
61047	55	ADHESIVE BOSTIK 7376
61048	1,253	POTTING COMPOUND POLYURETHANE DC902-1
61049	1,540	ZIPPER YGC 459
61050	551	FILM RUCOTHANE CO-A5154
61051	616	INSULATION FOAM GOLDEN WEST 9-12
61052	499	FABRIC TECKNIT 77-09-776
61053	1,540	ZIPPER TFE/FIBERGLASS/NOMEX
61054	436	FABRIC ANCHORAGE 2 BLUE 69/1211
61055	1,387	SEALANT FOMOFIX POLYURETHANE
61056	467	FABRIC NEOPRENE/NYLON CRP21757
61057		DELETED SEE 60738
61058	566	GLOVE HANDLING ANIMAL 645
61059	1,265	RECORDER STRIP CHART
61060	636	INSULATION FOAM PYRELL AFONIC ACCOUSTICAL POLYURETHANE
61061	480	FABRIC NOMEX/VELCRO/FC4101
61062	483	FABRIC NYLON MESH 8885
61063	704	LAMIN EPOXY/GRAPHITE HMF/34
61064	1,414	TAPE CHARTPAK GRAPHIC 5003 BLUE
61065	1,432	TAPE MYSTIK 7367/DC3140 COATING
61066	392	COATING URETHANE ASMBY
61067	526	FASTENER VELCRO POLYESTER LOOP 2000
61068	794	PEN PM BLACK/K-10 PAPER
61069	430	ENVEX 1000 POLYIMIDE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006712 8

MATCD	PAGE	DESIGNATION
61070	431	ENVEX 1330 POLYIMIDE/GRAPHITE
61071	430	ENVEX 1228 POLYIMIDE/PTFE
61072	1,403	SPLICES NYLON STA-KON
61073	686	LAMIN CMC608-2 POLYIMIDE WITH COPPER
61074	449	FABRIC DURETTE 400-7 NOMEX HT
61075	1,373	RUBBER VITON A V709-90
61076	448	FABRIC DURETTE 400-18 NOMEX HT
61077	693	LAMIN EPOXY/GLASS CE9010/181 KEVLAR 49
61078		DELETED SEE 05414
61079	1,373	RUBBER VITON A V23
61080	1,422	TAPE G408100 INCONEL SILICONE ADHESIVE
61081	88	ADHESIVE DENSIL 2078 SILICONE
61082		DELETED SEE 00016
61084	959	PLASTIC LEXAN F2000 POLYCARBONATE
61085	1,411	TAPE 2345-1 KAPTON/SILICONE
61086	71	ADHESIVE CHOBOND 1029
61087	72	ADHESIVE CHOBOND 1030
61088	1,488	TUBING GENCOTE 125C
61089	273	ADHESIVE URALITE 3124 POLYURETHANE RESIN
61090	1,303	RUBBER NEOPRENE NS105
61091	520	FASTENER VELCRO NYLON KRAYTON LOOP 1000 PS 0102
61093		DELETED SEE 06191
61094	547	FILM PHOTOGRAPHIC 667
61095	547	FILM PHOTOGRAPHIC 107 B & W
61096	616	INSULATION FOAM GRADE 1331
61097	612	INSULATION FOAM CPR9700
61098	616	INSULATION FOAM GRADE 1830
61099	1,288	RUBBER FLUOREL 5033
61101	396	COMPONENT BOARDS DC 1-2577
61102	620	INSULATION FOAM MOLECULON RP11 URETHANE
61103	1,421	TAPE G407700 KAPTON VACUUM DEPOSITED ALUMINUM WITH SILICONE ADHESIVE
61104	643	INSULATION FOAM STEPAN BX352 URETHANE
61105		DELETED SEE 60707
61106	695	LAMIN EPOXY/GLASS F164-1/7781
61107	607	INSULATION FOAM CHEMLON 500FC POLYIMIDE
61108	1,356	RUBBER SILICONE RTV R2567
61109	416	CORD KEVLAR
61110	1,516	WEBBING KEVLAR 1000 LB
61111	462	FABRIC KEVLAR
61112	1,355	RUBBER SILICONE RTV R2566
61113	722	LINE CASTING WHITE GHOST NYLON
61114	782	NYLON 12
61115		DELETED SEE 65421
61116	1,264	RAZOR GILLETTE TRAC II
61117	1,355	RUBBER SILICONE RTV R1500
61118	1,355	RUBBER SILICONE RTV R2500
61119	1,355	RUBBER SILICONE RTV R2510
61120	1,355	RUBBER SILICONE RTV R2520
61121	500	FABRIC TEFLON 30
61123	1,383	RUBBER VITON V779-75
61124	1,313	RUBBER PNF P39
61125	645	INSULATION FOAM TEMPERFOAM T38
61126	1,283	RUBBER EPR E617-9 ELASTOMER
61127	516	FASTENER VELCRO NYLON HOOK 65 BACKING PS 0102
61128		DELETED SEE 60911
61129	1,397	SEALANT ZINC/GREASE 21059
61130	1,388	SEALANT GAGEKOTE 3 SILICONE
61131	1,521	WEBBING POLYESTER 1754
61132	1,490	TUBING KORVEX FEP HS
61133	388	COATING SUPER KOROPON/LATEX433495
61134	152	ADHESIVE EPOXY PATCH KIT
61135	146	ADHESIVE EPOTEK H61
61136	674	LACING TAPE FRL 73300-130-5
61137		DELETED SEE 05215
61138	311	COATING 463-12-19 EPOXY PRIMER
61139	1,436	TAPE P213 GLASS ACRYLIC ADHESIVE
61140	429	EARPHONE HD-424
61141	373	COATING POLYURETHANE PR1546
61142	1,461	TAPE TA88 PS
61143	700	LAMIN EPOXY/GLASS XYLOK 210
61144	704	LAMIN EPOXY/KELVAR E707/KEVLAR 120
61145	143	ADHESIVE EPOTEK 320
61146	1,303	RUBBER NEOPRENE NS101
61147	1,474	TERMINAL STRIP 221 PHENOLIC
61148	490	FABRIC PHENOLIC/RESIN R1492Y12
61149	1,436	TAPE P223 TEFLON/AG
61150	1,396	SEALANT VITON AP2709
61151	601	INSULATION CORK
61152	593	INK PRINTERS A-M CS 174C BLACK
61153	336	COATING CONDUCTIVE 463-6-14
61154	286	BLADDER URETHANE
61155	110	ADHESIVE ECCOBOND 51/C11
61156	706	LAMIN EPOXY/KEVLAR F155
61157	707	LAMIN F120-150-1P20
61158		DELETED SEE 00030
61159	284	BATTERY MALLORY PX288
61160	483	FABRIC NYLON SILICONE COATED 1409
61161	149	ADHESIVE EPOXY 77
61162	487	FABRIC PBI FRL-73300-131
61163	494	FABRIC RCF 328-1C
61164	1,487	TUBING FLEX PLUROTUBE POLYURETHANE
61165	531	FILM 2104 PLASTIC
61166	710	LAMIN HMS/934/SONA30 EPOXY
61167	389	COATING TAPE PRIMER 81
61168	555	FILM VINYL GAUGE 8G
61171	497	FABRIC SILICONE/GLASS WITH ZIPPER
61172	1,403	SPATULA RUBBERMAID 1904
61173	786	PAPER CHART TYPE 58340
61174	523	FASTENER VELCRO POLYESTER HOOK 1 INCH
61175	545	FILM NYLON
61176	561	FUSE HOLDER
61177	411	CONNECTOR ELECTRICAL PLUG
61178	83	ADHESIVE CVV
61179	709	LAMIN FORTIN CORE 1111
61180	461	FABRIC HT-67-42 NOMEX NATURAL
61181	459	FABRIC HT-195-40 NOMEX
61182	409	CONNECTOR ELECTRICAL
61183	1,245	POTTING COMPOUND CASTALL A301/E34
61184	571	HEATER STRIP HK607005B

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006713 T

MATCD	PAGE	DESIGNATION
61185	512	FASTENER VELCRO NOMEX HOOK 0.75 INCH
61186	1,270	RUBBER AGC 3-126 CLASS 5
61187	1,506	VACUUM CLEANER HANDIVAC II
61188	513	FASTENER VELCRO NOMEX LOOP 1 INCH
61189	669	LABEL KRYLON ACRYLIC SPRAY-ON
61190	1,506	VALVE NON-REBREATHER
61191	362	COATING MC7755-03 TOPCOAT DC3140
61192	362	COATING MC7755-03 K1041 POLYURETHANE
61193	761	MICRO-SWITCH 12TL1-3
61194	761	MICRO-SWITCH 14TL1-3
61195	145	ADHESIVE EPOTEK H31LV
61196		DELETED SEE 60863
61197	488	FABRIC PBI FRL-73300-201 FX
61198	27	ADHESIVE AMICON C840-23 EPOXY
61199	26	ADHESIVE AMICON 845 EPOXY
61200	17	ADHESIVE ABLEBOND 41-1 EPOXY
61201	752	LUBE OIL FOMBLIN Y06
61202	134	ADHESIVE EPON 825/HV/MEK-V
61203		DELETED SEE 61901
61204	134	ADHESIVE EPON 825/HV
61205	133	ADHESIVE EPON 815/EPC190/AP5V
61206	99	ADHESIVE EA828/DER732/AEP/CABOSIL
61207	354	COATING HELASTIC X768 POLYURETHANE
61208	709	LAMIN FORTIN CORE 2121
61209	720	LBNPD NOMEX COVERED
61210	1,479	THREAD POLYESTER BLACK
61211	323	COATING ACRYLIC ENAMEL BLACK
61212		DELETED SEE 20566
61213	746	LUBE GREASE MOLYCOTE C40 CHAIN
61214	107	ADHESIVE EC1945 A/B
61215		DELETED SEE 05267
61216	361	COATING LATEX 3715-26-1 A/B
61217	428	DUCT VENT ASSEMBLY
61218	304	CLAMP NEOPRENE/AL MS21919DG
61219	1,474	TEFZEL ETFE
61220	409	CONNECTOR ELECTRICAL
61221	409	CONNECTOR ELECTRICAL
61222	409	CONNECTOR ELECTRICAL
61223	268	ADHESIVE UNISET D271 EPOXY
61224	1,425	TAPE KAPTON/GLASS/SILICONE JE4.10
61225	1,523	WIRE ELEC 16 AWG CABLE
61226	358	COATING KOROPON SUPER HI TEMP
61227	1,414	TAPE CASSETTE MEMOREX 120
61228	623	INSULATION FOAM NOPCO G306R/G306T
61230		DELETED SEE 20877
61232	175	ADHESIVE HEXABOND 3 FILM
61233	386	COATING SILICONE JUNCTION R6101
61234	673	LACING TAPE FRL 615-156 PBI
61235	678	LACING TAPE NOMEX 1342-300
61237	406	CONNECTOR DM5623-37-37 PP
61238	286	BOOT 05078 LEATHER/NYLON
61239	763	MOLD COMPOUND DAP FS6 CAF BLUE
61240	1,280	RUBBER DIATHON WATERPROOFING
61241	395	COATING XECOTE/OCF4190B WITH F017A
61242	395	COATING XECOTE/X389-7 TFE BETA
61243	567	GOGGLES SUN 8465-530-4083
61244	396	COMPASS MAGNETIC FSN6605-846-7618
61248	1,370	RUBBER VITON 744-75
61249	408	CONNECTOR ELECTRIC
61250	407	CONNECTOR ELEC JT06A-8-65(300)
61252	385	COATING SILCARB/CERAMIC AB312 FAB
61253	541	FILM METLBOND 1113-2 ADHESIVE
61254	1,475	THREAD CRES 304 MF-A1 28/61/5Z
61256	442	FABRIC COTTON NATURAL
61257	784	OINTMENT VASELINE CONSTANT CARE
61258	321	COATING A136 EPOXY
61259		DELETED SEE 61517
61260	1,418	TAPE FGA32600 ALUMINIZED
61261	1,383	RUBBER VITON V884-75
61262	722	LINER GLASS CLOTH 120/EPON 815
61263	1,388	SEALANT GRAPHITE FILLED TEFLON
61264	1,512	VYDAX 1000
61265	1,514	WEBBING DACRON 1695
61266	1,383	RUBBER VITON V894-90
61267	706	LAMIN EPOXY/KEVLAR F161
61268	1,397	SEALANT ZINC CHROMATE GRAY
61270	513	FASTENER VELCRO NOMEX LOOP 2000 BACKING 0199
61271	21	ADHESIVE ABLEFILM 546 KAPTON
61272	429	ELECTRICAL CONNECTOR WITH FIBERITE FM4051
61273	430	ELECTRICAL CONNECTOR WITH MOLD COMPOUND RX660
61274	1,490	TUBING KORVEX TFE HS
61275	561	FOOD RAT/MOUSE
61278	1,301	RUBBER NEOPRENE BC CWB10
61279	416	CORD ELASTIC NOMEX COVERED
61280	575	HOSE HYTRON PRESSURE
61281	435	FABRIC AIRC73300-233
61282	1,453	TAPE SCOTCH MAGIC TRANSPARENT
61283	1,373	RUBBER VITON A V745-75
61284	1,380	RUBBER VITON V672-7
61285	1,265	RECORDER MARS 1400
61286	572	HELMET ASTRONAUT
61287	319	COATING 850-204/851-225/856-204
61288	601	INSULATION CHOTRAP CM26-3
61289	1,500	TUBING STM SILICONE NO HST
61290	496	FABRIC SILICONE RUBBER/ARAMID
61291	439	FABRIC CERAMIC AB312 SILICONE COATED
61292	423	CURTAIN HYGIENE CLOSURE
61293	615	INSULATION FOAM ENSOLITE TYPE ALF POLYURETHANE
61294	543	FILM MYLAR 805 PURPLE/JCP E20
61295	542	FILM MYLAR 205 RED/JCP E20
61296	543	FILM MYLAR 505 ORANGE/JCP E20
61297	543	FILM MYLAR 615 LT GRN/JCP E20
61298	485	FABRIC NYLON/PVC TXN266
61299	229	ADHESIVE RELIABOND 382 EPOXY FILM
61300	104	ADHESIVE EA9628NW FILM
61301	1,447	TAPE SCOTCH 467
61302		DELETED SEE 06129
61303	756	LUBE SYNTON PAO 100
61306	405	CONNECTOR 2001-5119-00
61307	411	CONNECTOR MS2743E14F37PC

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006714 1

MATCD	PAGE	DESIGNATION
61308	413	CONNECTOR S-L-C28804-100-3N
61310	1,265	RAZOR RECHARGEABLE XLR900
61311	1,265	RAZOR XLR500
61312	412	CONNECTOR MS3456L20-15PW
61313	1,489	TUBING HS RT 1312 VITON
61314	108	ADHESIVE EC3924
61315	678	LACING TAPE NOMEX 1318X5
61316	678	LACING TAPE NOMEX 1317Z
61317	718	LAMIN TEXTOLITE 11508
61318	739	LUBE GREASE BRAYCO 814Z
61321	405	CONNECTOR 38108-24-61S
61322	9	ADHESIVE 4914 ACRYLIC
61324	19	ADHESIVE ABLEBOND 770-6 EPOXY
61325	644	INSULATION FOAM STYROFOAM TG BLUE
61327	437	FABRIC AROMATIC POLYAMIDE
61328	1,292	RUBBER FLUOROSILICONE LS2323
61331	1,374	RUBBER VITON A V86-678
61332	625	INSULATION FOAM PHENEXPAN P40/P80
61333	1,326	RUBBER SILICONE 4524
61334	192	ADHESIVE MEL 20
61335	1,408	SPONGE RUBBER SILICONE PR855 FR
61338	448	FABRIC DURETTE 400-36 NOMEX
61339	533	FILM BONDING XC453
61340	1,425	TAPE KAPTON/AL METALIZED KN80
61341	758	MARKER METALLIC NIJI SILVER
61342	757	MARKER METALLIC NIJI GOLD
61343	752	LUBE OIL FLUOROLUBE FS-5
61345	315	COATING 6543U/PRIMER 8245
61346	1,287	RUBBER FAIRPRENE DS0001
61347	694	LAMIN EPOXY/GLASS DX501/7581/181
61348	204	ADHESIVE NEOPRENE 61015
61349	567	GLUE ELMERS
61350	1,414	TAPE CASSETTE MC60
61355	297	CAPACITOR EMI TVA1966
61357	795	PEN SHARPIE 35001
61358	540	FILM KODAK TX135-36
61359	540	FILM KODACHROME 64 KR135-36
61360	274	ADHESIVE URETHANE RP6401
61361	651	INSULATION FOMO FILL
61362	419	CORD POLYESTER .0625 NATURAL
61363	1,409	SPONGE RUBBER SILICONE PR855-2 FR
61364	312	COATING 463-12-19 PRIMER
61365	1,389	SEALANT KOPR-SHIELD
61366	761	METER SOUND LEVEL 2215
61367	1,401	SLIPPER SOCKS
61368	43	ADHESIVE ARMSTRONG ACTA 1 RESIN
61371	287	BRAID ELASTIC POLYESTER
61372	715	LAMIN POLYETHYLENE/SARANEX 23
61376	39	ADHESIVE AREMCOBOND 517 EPOXY
61378	457	FABRIC GLASS/SILICONE SRG1817
61379	66	ADHESIVE CAVALON 3300S/3101S
61380	294	CABLE MICROPHONE
61381	404	CONNECTOR 15-319D
61384	446	FABRIC DACRON/VITON FD5318
61385	446	FABRIC DACRON/SILICONE RUBBER SRD5210
61386	666	LABEL GRAVOFLEX
61388	547	FILM PHOTOGRAPHIC 7294
61390	517	FASTENER VELCRO NYLON HOOK 65 LOOP 1000 BACKING 9999
61391	517	FASTENER VELCRO NYLON HOOK 65 LOOP 1000 BACKING 2899
61392	358	COATING KONFORM SILICONE
61394		DELETED SEE 60239
61395	1,264	PUMP MICRO
61396	679	LACING TAPE NOMEX RD1251Z
61397	517	FASTENER VELCRO NYLON HOOK 65 LOOP 1000 BACKING 1299
61398	517	FASTENER VELCRO NYLON HOOK 65 LOOP 1000 BACKING 0399
61399	679	LACING TAPE NOMEX/VITON 1342C
61400	675	LACING TAPE HT-30 LOC A NOMEX
61401	676	LACING TAPE HT-30-VR
61402	616	INSULATION FOAM ETHAFOAM 220/RUBBER RTV 560
61403	658	INSULATION TG15000/SCOTCH 853 TAPE
61404	657	INSULATION TG15000/MYLAR/FEP TAPE
61405	657	INSULATION TG15000/MYLAR/L-T-80 TAPE
61406		DELETED SEE 01036
61407	1,501	TUBING TEFLON TFE HST
61408	1,536	YARN NOMEX R79-430
61409	1,456	TAPE SCOTCH YR364 ALUMINUM GLASS WITH SILICONE ADHESIVE
61410	767	MOLD COMPOUND FIBERITE FM-8130
61411	764	MOLD COMPOUND DUREZ 11844 BLK
61412	691	LAMIN EPOXY/GLASS 7070664
61413	187	ADHESIVE LOCTITE A
61414	186	ADHESIVE LOCTITE 75
61415	187	ADHESIVE LOCTITE E/LOCTITE T PRIMER
61416	306	CLAMP WITH SILICONE INSERT
61417	525	FASTENER VELCRO POLYESTER HOOK H549 FR127A ADHESIVE
61418	1,356	RUBBER SILICONE S317
61419	528	FELT NOMEX S2335 NRB/Z
61420	1,364	RUBBER SILICONE WITH WIRE MESH
61421	785	ORBITER RADIATOR COVER
61422	756	LUBE TEFLON PTFE SPRAY
61423	497	FABRIC SILICONE/GLASS GS200
61424	314	COATING 515-700/910-704 CATALYST
61425	697	LAMIN EPOXY/GLASS GENERAL PURPOSE
61426	696	LAMIN EPOXY/GLASS FR TYPE GF
61427		DELETED SEE 05056
61428	716	LAMIN POLYIMIDE/GLASS
61429	958	PLASTIC LEXAN 9600 NATURAL POLYCARBONATE
61431	351	COATING EPOXY/POLYIMIDE
61432	696	LAMIN EPOXY/GLASS F164/7781
61434		DELETED SEE 61267
61435	695	LAMIN EPOXY/GLASS F164
61436	695	LAMIN EPOXY/GLASS F164-1
61437		DELETED SEE 05137
61438		DELETED SEE 61431
61439	351	COATING EPOXY/POLYAMIDE CONVERT

MSFC-HDBK-527 REV F 9999942 0006715 3

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
61440	1,413	TAPE ALUMINUM FOIL M90006 ADHESIVE
61442	683	LACING TAPE STUR-D-LACE 18DR-E
61443	689	LAMIN EPOXY/BORON/TITANIUM SHEET
61444		DELETED SEE 05447
61445	552	FILM TEDLAR 200BG30 PVF
61446	169	ADHESIVE FOAM AF3018 EPOXY
61447	169	ADHESIVE FOAM EA9814 EPOXY
61448		DELETED SEE 61085
61449	585	INK CAT-L-INK 50-700R/9
61450	310	COATING 401-C10 BLACK
61451	715	LAMIN POLYIMIDE HI3003
61452	717	LAMIN POLYIMIDE/GLASS MICAPAK PG402T
61453	716	LAMIN POLYIMIDE/GLASS HI3000
61454	717	LAMIN PRINTED WIRING BOARD /DC3140 COATED
61455	777	MULTI-LAYERED INSULATION DACRON NET B4A/TG15000 SILICONE GLASS/KAPTON/PBI
61456	777	MULTI-LAYERED INSULATION DACRON NET B4A/ POLYBENZIMIDAZOLE/TG15000 SILICONE GLASS/TAPE G411970 ALUMINUM/KAPTON
61457	777	MULTI-LAYERED INSULATION DACRON NET B4A/ALUMINUZED KAPTON/PBI/ALUMINIZED KAPTON RIPSTOP
61458	777	MULTI-LAYERED INSULATION DACRON NET B4A/KAPTON/ ALUMINUM/PBI
61459	1,410	STRAP ELEC AL KAPTON/PBI
61460	777	MULTI-LAYERED INSULATION DACRON NET B4A/GOLDIZED KAPTON/TG15000 SILICONE GLASS/G411660
61461	1,446	TAPE SCOTCH 425 PS
61462		DELETED SEE 05177
61463	17	ADHESIVE ABLEBOND 463-1 EPOXY/AG FI11
61465	770	MOLD COMPOUND PLENCO 1528
61466	228	ADHESIVE RAPIDSET BLUE EPOXY
61467	1,259	POTTING COMPOUND STYCAST 2651/C9
61468	1,284	RUBBER EPR E810-80
61469	1,291	RUBBER FLUOROSILICONE
61470	317	COATING 821-400 POLYURETHANE GLOSS WHITE
61471	316	COATING 821-331 POLYURETHANE FLAT WHITE
61473		DELETED SEE 05202
61474		DELETED SEE 61219
61475	698	LAMIN EPOXY/GLASS N4105
61476	305	CLAMP SILICONE/CRES JM44
61477	289	CABLE CLAMP ME 127-0071
61478	703	LAMIN EPOXY/GRAPHITE F263
61479	1,458	TAPE SCOTCHLITE 3290 VINYL PS
61480	474	FABRIC NOMEX HT-49
61481		DELETED SEE 05142
61482	692	LAMIN EPOXY/GLASS B10-108-63
61483	243	ADHESIVE SCOTCHWELD XA3950
61487	69	ADHESIVE CHEMLOK 234
61488	763	MOLD COMPOUND DAP SDG 6120
61489	700	LAMIN EPOXY/GLASS TYPE GF
61490	674	LACING TAPE GUDE-SPACE 18DPT-H
61491	673	LACING TAPE BRAID NYLON
61492	1,478	THREAD PBI FRL-S152
61493	778	MULTI-LAYERED INSULATION KAPTON AU OUTER KAPTON AL
61494	1,322	RUBBER SILASTIC LT40/WHITE
61495	1,322	RUBBER SILASTIC LT40/RED
61496	1,420	TAPE G402410 VACUUM DEPOSITED ALUMINUM 1 MIL KAPTON
61499		DELETED SEE 05510
61500	1,428	TAPE MARKING 02
61501	1,323	RUBBER SILASTIC RTV 732 CL 2
61502	760	MERLON M-50U POLYCARBONATE
61505	59	ADHESIVE C9-4210 AND 4215/H3469 EPOXY
61506	1,344	RUBBER SILICONE RTV 281-400S
61508	1,363	RUBBER SILICONE TH1241
61509	1,340	RUBBER SILICONE PRE100-40R
61510	1,306	RUBBER NITRILE
61511		DELETED SEE 01784
61512	1,307	RUBBER NITRILE CPD 7377
61513	1,306	RUBBER NITRILE 1070W VIX
61514	700	LAMIN EPOXY/GLASS TAYLORCLAD FIREBAN
61516	1,461	TAPE TEFLON
61517	393	COATING VARNISH 961
61518	412	CONNECTOR NB-CR-20
61519	412	CONNECTOR NB-CS-20
61520	412	CONNECTOR NB-CS-16
61521	412	CONNECTOR NB-GSP-16
61522	412	CONNECTOR NB-GSP-20
61523		DELETED SEE 61103
61524	667	LABEL IDENTIFICATION MYLAR ADHESIVE 850 CLEAR
61525	667	LABEL IDENTIFICATION MYLAR ADHESIVE 850/RED
61526	668	LABEL IDENTIFICATION MYLAR ADHESIVE 850/SILVER
61527	497	FABRIC SILICONE/GLASS 3016
61529	789	PAPER NOMEX TYPE 410/ARAMID
61530	690	LAMIN EPOXY/GLASS
61531	437	FABRIC AROMATIC/NON-MELTING
61532	648	INSULATION FOAM URETHANE BLACK
61533	636	INSULATION FOAM PYRELL PC210 COATING
61534	638	INSULATION FOAM PYRELL/FC273 COATING
61535	638	INSULATION FOAM PYRELL/RTV 3140 COATING
61537	706	LAMIN EPOXY/KEVLAR F164-1/181
61539	1,272	RUBBER BUTYL
61540	605	INSULATION FOAM CEI 10 FLUOROCARBON
61541	1,526	WIRE ELEC FLEXIBLE PRINTED/KAPTON
61542	223	ADHESIVE PR175082 POLYSULFIDE
61543	1,496	TUBING POLYOLEFIN RET125 HST
61544	676	LACING TAPE HT-30-TVS NOMEX
61546	338	COATING CPC3864 WHITE EPOXY
61547	1,462	TAPE TEFLON PATTERN 2338
61548	681	LACING TAPE PBI/VITON 1330V
61549	337	COATING CPA5197 GREY EPOXY
61550	778	MULTI-LAYERED INSULATION KAPTON/ALUMINUM/TG15000 SILICONE GLASS/DACRON NET B4A/PBI
61551	365	COATING NYEBAR TYPE CT
61552		DELETED SEE 06007
61553		DELETED SEE 05039
61555	501	FABRIC TEFLON T9362/TFE COATED
61557		DELETED SEE 06095
61558	546	FILM P188-5/1 KAPTON/ACRYLIC
61559	705	LAMIN EPOXY/KEVLAR E42

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006716 5

MATCD	PAGE	DESIGNATION
61560	72	ADHESIVE CHOBOND 350A/B WITH 1086PRI
61561	1,421	TAPE G406400/G406402 VACUUM DEPOSITED GOLD AND 1 MIL KAPTON WITH ACRYLIC ADHESIVE
61562	578	HOSE REDAR SI644-01 SILICONE
61564	1,303	RUBBER NEOPRENE NS106
61565	1,488	TUBING G10 130C FIBERGLASS/EPOXY
61566	1,431	TAPE MYSTIK 7000 GLASS/SILICONE ADHESIVE
61567	1,431	TAPE MYSTIK 7001 GLASS/SILICONE ADHESIVE
61568	1,455	TAPE SCOTCH Y434 SOUNDDAMP ALUMINUM FOIL
61569	1,485	TUBING FERREX 01-0504 SILICONE
61570	1,538	ZIPPER ASSEMBLY NOMEX
61571	496	FABRIC SILICONE/ARAMID7311NHT6
61572	237	ADHESIVE SCOTCHGRIP 847
61573	959	PLASTIC LEXAN F6000 POLYCARBONATE
61574	1,463	TAPE TEFLON/ACRYLIC 5396
61575	1,491	TUBING KYNAR CONVOLUTED/SS COVR
61576	1,418	TAPE FLUORGLAS ALUMINUM/GLASS SILICONE ADHESIVE
61577	378	COATING PRIMER LOCTITE GR-T
61578	75	ADHESIVE CONAPOXY FR1241/EA4
61579	363	COATING METALOX/31G6/11X2/50C3
61580	1,301	RUBBER NEOPRENE
61581		DELETED SEE 05658
61582	470	FABRIC NOMEX 7878 G650/FC5
61583	599	INSULATION AFRSI WITH DISILAZANE Z6079
61584	599	INSULATION AFRSI WITH SILANE Z6070
61585	658	INSULATION TG15000/TI/TAPE 853/KAP
61586	1,425	TAPE KAPTON/NYLON ACRYLIC LOT 20
61587	1,419	TAPE FLUORGLAS/TEFLON
61589	795	PEN SHARPIE 3000 BLK
61590	662	KEL-F 81 EXPANDED/BLUE BEADING
61591	404	CONFIG VITON RT876/THERMOFIT
61592	317	COATING 822-326 PRIMER
61593	471	FABRIC NOMEX 9476
61595	1,489	TUBING HYGRADE SR398 HA1
61596	1,486	TUBING FIBERGLASS/SILICONE 3298-1
61597	1,379	RUBBER VITON SHORE A
61598	1,384	RUBBER VITON VL1502-H141
61599	567	GRAPHITAR G36-295
61600		DELETED SEE 20435
61601	378	COATING PRIMER P605-66/C152-66 BLUE
61603	359	COATING L496A-66/37038 CAM LACQURE
61604	330	COATING CAT-A-LAC 463-3-8/C118
61605	354	COATING HELASTIC 25GD102
61606		DELETED SEE 05173
61607		DELETED SEE 20301
61608	1,417	TAPE ELASTIC 14738P/B8209W
61609		DELETED SEE 60474
61610	288	BRAKE MATERIAL M4952
61611	1,410	STRAP NEOPRENE/COTTON/RUBBER
61612	1,497	TUBING POLYVINYLFLOURIDE K46 HS
61613		DELETED SEE 20477
61614		DELETED SEE 60488
61615	623	INSULATION FOAM OMALON 3
61616	419	CORD NYLON BRAIDED 50
61617		DELETED SEE 20499
61618	1,066	PLASTIC POLYSULFONE P1700
61619	1,314	RUBBER POLYURETHANE X364
61620	1,314	RUBBER POLYURETHANE RUCOTHANE AX5225 WITH COTTON FLOC
61621	1,315	RUBBER POLYURETHANE X364 RUCOTHANE/5154
61622	1,314	RUBBER POLYURETHANE RUCOTHANE 5154 WITH COTTON FLOC/RED PIGMENT
61623	1,405	SPONGE RUBBER NEOPRENE CLOSED CELL KNIT
61624		DELETED SEE 60636
61625	147	ADHESIVE EPOTEK H77
61626	1,289	RUBBER FLUOROCARBON
61627	1,380	RUBBER VITON V709-90
61628		DELETED SEE 61283
61629	1,268	REVAC DD2010
61630	184	ADHESIVE LOCTITE 241
61631	306	CLAMP TEFLON PTFE
61632	250	ADHESIVE SK43 SILICONE
61633	492	FABRIC POLYETHER POLYURETHANE COATED NYLON
61634	438	FABRIC BETA/SILICONE S85035
61635	720	LEAD TAXCHEM MARKING 200 GREEN
61636	761	MICROPHONE HANDHELD PLUG/CABLE
61637	469	FABRIC NOMEX 3 WICKWELL FINISH
61638	468	FABRIC NOMEX 3 ARAMD/NO FINISH
61639	469	FABRIC NOMEX 3/SCOTCHGARD COATED
61640		DELETED SEE 60863
61641	134	ADHESIVE EPON 826/BDE/T6040
61642	297	CARBON FIBER TOW AS4W
61643	406	CONNECTOR ELEC 27473E8F35P
61645	414	CONNECTOR TAPE RECORDER
61646	412	CONNECTOR P/N 2075060
61647	414	CONNECTOR TAPE RECORDER
61648	662	KEL-F 81 PV 506 GASKET
61649	600	INSULATION BLANKET FLUORGLAS 385-3
61650	1,266	REGULATOR VICTOR SR250D
61651		DELETED SEE 60635
61652		DELETED SEE 20006
61653		DELETED SEE 60609
61654		DELETED SEE 61543
61655		DELETED SEE 60636
61656	1,495	TUBING POLYOLEFIN GPO135 T2
61657	509	FASTENER VELCRO HI-MEG NYLON LOOP IMPREGNATED WITH SILVER
61658	519	FASTENER VELCRO NYLON HOOK HI-MEG
61659	779	MULTI-LAYERED INSULATION KAPTON/NOMEX/AU/TG 15000
61660	1,521	WEBBING NYLON/VELCRO/NOMEX/METALIZED UTILITY STRAP
61661		DELETED SEE 60987
61662	1,364	RUBBER SR2702-75
61663	394	COATING WD40
61664	677	LACING TAPE NOMEX 1251VC
61665	738	LUBE GREASE AIRCRAFT
61667	1,269	RUBBER 10006149
61668	316	COATING 7414/PRIMER EPOXY 8245
61669	654	INSULATION MYLAR ALUMINIZED TYPE 2
61670	488	FABRIC PBI FRL-73300-197 FX
61671	488	FABRIC PBI FRL-73300-197

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006717 7 ■

MATCD	PAGE	DESIGNATION
61672	958	PLASTIC LEXAN 9604 FR NATURAL POLYCARBONATE
61673		DELETED SEE 05042
61674		DELETED SEE 05005
61675	605	INSULATION FOAM CHEMLON 100TA NRL2-2
61676	521	FASTENER VELCRO NYLON LOOP 1000 PS 0140
61679	501	FABRIC TREVIRA POLYEST 203 GRN
61680	1,387	SEALANT FLUOROCARBON MS83248/2-904
61681	1,387	SEALANT FLUOROCARBON M83248/2-916
61682	133	ADHESIVE EPON 815/EPC190/AP5
61685	552	FILM SARAN PSD629/200GA CLEAR
61686	1,426	TAPE KAPTON/NYLON OT21
61687	514	FASTENER VELCRO NYLON HOOK 0100
61689	469	FABRIC NOMEX 3/ZEPEL FINISH
61690	712	LAMIN MICAPLY EG818T
61691	623	INSULATION FOAM NORYL FN215
61692	959	PLASTIC LEXAN FL900
61693	572	HOMALITE H-911 POLYESTER
61694	586	INK DICK-B-4020C ON JCP E20
61695	1,263	POWER SUPPLY UPM15/100 ASSEMBLY
61697	529	FELT NOMEX STYLE 190R
61698	602	INSULATION FELT NOMEX TYPE E
61699	603	INSULATION FOAM 402 POLYURETHANE
61700	5	ADHESIVE 18540 11C/EPON H2 CURE
61701	467	FABRIC NEOPRENE/NYLON 18540-33
61702	687	LAMIN CORLAR 5134/KEVLAR 49-181
61703	281	ATTENUATION PAD HRH-10 1/8-4.0
61704	656	INSULATION SILICONE THERMAL
61705	464	FABRIC KEVLAR STYLE FDI043
61706	366	COATING ONCOR M50/ZNCHR 4334-109
61707	533	FILM CMC8-14-1A POLYIMIDE
61708	1,290	RUBBER FLUOROELASTOMER 2401B
61709	426	DESTRUX QC SEAL
61710	1,390	SEALANT POLYESTER
61711	591	INK MARKING RED
61712	590	INK MARKING BLUE
61713	590	INK MARKING BLACK
61714	591	INK MARKING WHITE
61715	132	ADHESIVE EPON 815/CAT Z EPOXY
61716	273	ADHESIVE URALANE 8267 POLYURETHANE
61717	1,034	PLASTIC PES-200P
61718	688	LAMIN EDGE LIGHT PANEL EPOXY/GLASS/ACRYLIC/VINYL
61719	711	LAMIN KERIMID 601/KEVLAR 49-181
61720	686	LAMIN CORLAR 5105/KEVLAR 49-181
61721	687	LAMIN CORLAR 6113/KEVLAR 49-181
61722	687	LAMIN CORLAR 6101-2/KEVLAR 49-18
61723	373	COATING POLYURETHANE PR1120
61724	341	COATING DC Z6031 SILANE
61725	686	LAMIN CORLAR 4102/KEVLAR 49-181
61726	717	LAMIN PYRALIN 3001/KEVLAR 49-181
61727	717	LAMIN PYRALIN 3003/KEVLAR 49-181
61728	711	LAMIN KEVLAR 49-181/SKYBOND 703
61729	1,482	TRANSCEIVER UHF
61730	1,413	TAPE ARMAFLEX LA3500 10-67 PS
61731	326	COATING ARMAFLEX VINYL
61732	1,424	TAPE KAPTON K107 GOLD REINFORCED
61733	791	PAPER TYVEK STYLE 1073D
61751		DELETED SEE 00030
61752	691	LAMIN EPOXY/GLASS
61753	1,117	PLASTIC SHEET SARNEX #15
61754	399	COMPOUND EPOXY 8013R/8012H
61755	134	ADHESIVE EPON 825/EPICURE 855
61756	648	INSULATION FOAM URETHANE FR Q31
61757	644	INSULATION FOAM STYRENE 4486
61758	352	COATING FUSECOTE/A34 EPOXY
61759	1,254	POTTING COMPOUND REN RP6401A POLYURETHANE BLUE
61760	1,254	POTTING COMPOUND REN RP6402A POLYURETHANE RED
61761	348	COATING EPOXY A117-B
61762	232	ADHESIVE RUBINATE M/VITEL PE307
61763	693	LAMIN EPOXY/GLASS CE9010
61764	664	KYNAR 460
61765	477	FABRIC NOMEX TWILL 60Z NATURAL
61766	961	PLASTIC LEXAN SL29
61767	617	INSULATION FOAM HYPOL 4 URETHANE
61768	503	FABRIC WOOL FLOVAN TREATED
61769	414	CONNECTOR SILICONE/RUBBER 40S
61770	648	INSULATION FOAM URETHANE FR G73C
61771	654	INSULATION PAPER ARMITE SLOT
61773	412	CONNECTOR PC BOARD DAP/ORLON
61774	310	COATING 4367-3 ON LAMIN 515-700
61775	21	ADHESIVE ABLEFILM 501
61776	270	ADHESIVE UNISET T530
61777	694	LAMIN EPOXY/GLASS E720E/7581 FR
61778	307	COATING 03-BK-28 WITH CATALYST
61779	353	COATING GRAY TOPCOAT/KOROPON PRIMER
61780	1,506	VALVE SUPERIOR 430
61781	1,115	PLASTIC RYTON PPS
61782	757	MAGNET 2V PERMENDUR
61783	1,263	PRESSURE VESSEL COMPOSITE
61784	1,499	TUBING SILICONE SR200 #18
61785	706	LAMIN EPOXY/KEVLAR E720E FR 49-120
61786	1,465	TAPE TEMP-R-TAPE T155
61787	1,465	TAPE TEMP-R-TAPE TV350
61788	706	LAMIN EPOXY/KEVLAR F164/KEVLAR 49
61789		DELETED SEE 05764
61790	366	COATING ONCOR M50 LATEX
61791	1,506	VALVE OXYGEN CHECK
61792	1,242	PNEUMATIC SURGE TEST FIXTURE
61793	634	INSULATION FOAM POLYURETHANE/AL TAPE L-T-80
61794	672	LACING TAPE 217
61795	638	INSULATION FOAM PYRELL/PRESTO 765/UT
61796	641	INSULATION FOAM SCOTTFELT 10-900 FR POLYURETHANE
61797	252	ADHESIVE SPRAY 76
61798	570	HALAR 300 CTFE/ETHYLENE
61799	298	CELCON G-C25 ACETAL/25% GLASS
61800	719	LAMIN/EPOXY/EPOCAST 1468/FYROL FR2
61801	723	LINER HOSE AE 116-8/AE 121-4
61802	723	LINER HOSE AE 246-10/667-16
61803	1,371	RUBBER VITON 8946
61804	1,304	RUBBER NEOPRENE SN100
61805	712	LAMIN KEVLAR/PR1660/10% PHOSGRD

MSFC-HDBK-527 REV F 9999942 0006718 9

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
61806	1,410	STRAP GROUNDING TCS NOMEX/KAPTON
61807	76	ADHESIVE CONBOND 2103 N/F
61808	76	ADHESIVE CONBOND 1560 N/F
61809	1,508	VELOSTAT 1810 SERIES
61810	654	INSULATION NOMEX 410/KAP/LDR PAPER
61811	1,283	RUBBER EPR AS014
61812	677	LACING TAPE NOMEX 1251V
61813	688	LAMIN EPOXY AP3012A
61814	1,285	RUBBER EPR ORINGS NS014 E59
61815	678	LACING TAPE NOMEX 1316
61816	677	LACING TAPE NOMEX 1251
61817	649	INSULATION FOAM URETHANE KUA100U-7LF
61818	649	INSULATION FOAM URETHANE KUA50-7LF
61819	648	INSULATION FOAM URETHANE J52924
61820	580	HOSE TEFLON TFE R736
61821		DELETED SEE 61820
61822	1,517	WEBBING NOMEX 14.4OZ
61823	1,517	WEBBING NOMEX 22.4OZ
61824		DELETED SEE 20569
61825	289	CABLE ASSEMBLY NYLON/GLASS
61827	655	INSULATION POLYURETHANE SHEET 4050
61828	659	INSULATIOON POLYURETHANE SHEET 4070
61829	477	FABRIC NOMEX TWILL 6OZ RED
61830	477	FABRIC NOMEX TWILL 6OZ BLACK
61831	477	FABRIC NOMEX TWILL 6OZ GOLD
61832	469	FABRIC NOMEX 30939 2.5OZ BROWN
61833	470	FABRIC NOMEX 30939 2.5OZ WHITE
61834	469	FABRIC NOMEX 30939 2.5OZ ORNG
61835	495	FABRIC SILICA C1154-48
61836		DELETED SEE 06039
61837		DELETED SEE 61145
61838	1,283	RUBBER EPR AP3013
61839	583	INK B5749/JCP K10 LITHO-ITEK
61840	583	INK A-M CS174C/JCP K10 BLACK
61841	650	INSULATION FOAM/KEVLAR PR1660/SEAL 2030
61842	649	INSULATION FOAM URETHANE L200
61843	644	INSULATION FOAM STYRENE 5486
61844		DELETED SEE 61757
61845	651	INSULATION GLASS/PHENOLIC M-P-AA-W
61846	1,334	RUBBER SILICONE DC93-500
61847		DELETED SEE 05283
61848	534	FILM CRONOPAQUE PETP/VINYL
61849	619	INSULATION FOAM LAST-A-FOAM POLYURETHANE FR6709
61850		DELETED SEE 60860
61851	1,443	TAPE REINFORCED 536-34-2 GOLD
61852	319	COATING 828-310 PRIMER
61853	318	COATING 823-311 PRIMER
61854	317	COATING 822-327 GRAY 36231 OVER MBO125-055 PRIMER
61855	309	COATING 03-Y-30 PRIMER
61856	708	LAMIN FIBERITE 1
61857	436	FABRIC ARAMID 3/K-GUARD 787818
61858	1,476	THREAD KEVLAR B132
61859	351	COATING EPOXY/SILICATE 193
61860	1,252	POTTING COMPOUND EPOXY/SILICATE ES218
61861	1,252	POTTING COMPOUND EPOXY/SILICATE ES180
61862	650	INSULATION FOAM URETHANE/POLYETHER N GREY
61863	1,475	THREAD GORE-TEX S012T3 PTFE
61864	334	COATING CHEMGLAZE Z306/AP131
61865	1,406	SPONGE RUBBER NEOPRENE R422N
61866	496	FABRIC SILICONE/ARMID 7311K120
61867		DELETED SEE 05547
61868		DELETED SEE 06051
61869	779	MULTI-LAYERED INSULATION KAPTON/BETA
61870	303	CLAMP CUSHION SILICONE/FIBERGLASS CL 3B GR 60
61871	1,406	SPONGE RUBBER NEOPRENE STY36-2V 40LB
61872		DELETED SEE 20391
61873	501	FABRIC TREVIRA POLYESTER 271
61874	497	FABRIC SPACER 6027-1-1
61875	1,289	RUBBER FLUOREL 5767-1
61876	1,289	RUBBER FLUOREL 5823
61877	307	COATING 03-BK-29 PRIMER
61878	308	COATING 03-GY-62 GRAY OVER MBO125-055 PRIMER
61879	1,382	RUBBER VITON V769-60
61880	1,382	RUBBER VITON V763-60
61881	577	HOSE PARFLEX 558H/POLYESTER
61882	576	HOSE PARFLEX 540N/POLYURETHANE
61883	319	COATING 850-204/851-245/856-204
61884	492	FABRIC POLYIMIDE FIBER
61885	412	CONNECTOR PC BOARD 10-398050-1P
61886	360	COATING LAC37-722A TY2/TT-P1757
61887	346	COATING ENAMEL C144
61888	744	LUBE GREASE HYDROCARBON AF419
61889	737	LUBE GREASE AEROSHELL XSG6249
61890	716	LAMIN POLYIMIDE/GLASS F178/7781
61891	1,374	RUBBER VITON CPD 8760
61892	1,305	RUBBER NEOTEX ELASTIC
61893	1,435	TAPE P051 ACRYLIC TRANSFER
61894	158	ADHESIVE EPOXYLITE CF8628 COATING
61895	130	ADHESIVE EPOCAST 290/9810
61896		DELETED SEE 02897
61898	1,441	TAPE POLYKEN 224A
61899	1,441	TAPE POLYKEN 234A
61900	516	FASTENER VELCRO NYLON HOOK 65 BACKING 9999
61901	515	FASTENER VELCRO NYLON HOOK 65 BACKING 0199
61902	520	FASTENER VELCRO NYLON LOOP 1000 BACKING 0199
61903	515	FASTENER VELCRO NYLON HOOK 65 BACKING 0399
61904	520	FASTENER VELCRO NYLON LOOP 1000 BACKING 0399
61905	521	FASTENER VELCRO NYLON LOOP 1000 BACKING 2699
61906	520	FASTENER VELCRO NYLON LOOP 1000 BACKING 1299
61907	521	FASTENER VELCRO NYLON LOOP 1000 BACKING 2899
61908	515	FASTENER VELCRO NYLON HOOK 65 AND LOOP 1000 BACKING 0199
61909	510	FASTENER VELCRO HOOK 80 LOOP 2000
61910	518	FASTENER VELCRO NYLON HOOK 80 BACKING 0104
61911	582	INK 4295/JCP K10 BROWN
61912	582	INK 4205/JCP K10 GREEN
61913	581	INK 4025/JCP K10 YELLOW
61914	581	INK 4085/JCP K10 RED
61915	582	INK 4115/JCP K10 VIOLET
61916	582	INK 4415/JCP K10 BLACK

MSFC-HDBK-527 REV F 9999942 0006719 0

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
61917	582	INK 4145/JCP K10 BLUE
61918	1,265	RECEPTACLE MS27503Y8E-35P
61919	1,428	TAPE LOOP-TAPE NYLON 1234
61920	556	FILTER MEDIA TFE GORE-TEX
61921	592	INK PARKER/JCP E20
61922	1,385	SCREEN TEFLON FEP/FIBERGLASS
61923	1,313	RUBBER PNF INORGANIC
61924	1,467	TAPE VINYL/COTTON TUCK 91B
61925	1,467	TAPE VINYL/COTTON SP252
61926	1,503	TUBING TYGON B44-3
61927	150	ADHESIVE EPOXY EPY150
61928	1,391	SEALANT POLYSULFIDE PR385M
61929	150	ADHESIVE EPOXY ER825A
61930	466	FABRIC MODACRYLIC 6901-1151
61931	448	FABRIC DURETTE 400-37 NOMEX HT
61932	575	HOSE LINER/R762-8 HOSE
61933		DELETED SEE 20577
61934	1,427	TAPE LEAD FOIL 420
61935	1,441	TAPE POLYKEN 207 COTTON
61936		DELETED SEE 06084
61937	705	LAMIN EPOXY/KEVLAR 120
61938	426	DESICCANT NBR48213
61939		DELETED SEE 05275
61940	466	FABRIC MULTI FIL G1106-80MZL
61941	528	FELT NOMEX 61HT/14
61942	1,371	RUBBER VITON 8846
61945	444	FABRIC COTTON WESTEX TWILL
61946	443	FABRIC COTTON SHIRTING/TOPSOFT
61947	444	FABRIC COTTON WESTEX SATINE
61948	443	FABRIC COTTON SHIRTING MC PP1
61949	444	FABRIC COTTON TWILL SHIRTING
61950	443	FABRIC COTTON SHAPE-FLEX LINING
61951	1,255	POTTING COMPOUND SCOTCHCAST 226 A/B
61952	685	LAMIN ACRYLACON/FIBERGLASS RNF
61953	712	LAMIN KYDEX ACRYLIC/PVC ALLOY
61954	708	LAMIN FIBERGLASS TA88
61955	563	GASKET SILICONE RUBBER
61956	1,397	SEALS K-6 LEAD COATED
61957		DELETED SEE 61239
61958	417	CORD KEVLAR 29 73457
61959	771	MOLD COMPOUND POLYSULFONE P-1720
61960	440	FABRIC COTTON 2701 FR
61961	1,393	SEALANT SILICONE
61962		DELETED SEE 20011
61963	10	ADHESIVE 76/KUA FOAM
61964	470	FABRIC NOMEX 7.5 OZ/ZEPEL
61965	1,417	TAPE ELASTIC RUBBER
61966	668	LABEL IDENTIFICATION PAPER DOTS GREEN
61967	1,442	TAPE PS C706 BLUE
61968	1,430	TAPE MYSTIK 6375 PAPER/PS GREEN
61969	1,277	RUBBER COHRLASTIC 700 SILICONE
61970	295	CABLE TIES MOUNT TC103 NYLON
61971	569	GROMMET NEOPRENE
61972	657	INSULATION STYROFOAM/STYRENE
61973	1,394	SEALANT SILICONE SIL-PADS 400
61974	304	CLAMP ELECT NYLON/GLASS FILLED
61975	490	FABRIC POLYESTER KK14 FR
61976	658	INSULATION URETHANE UNIFOAM S82N
61977	446	FABRIC DACRON PACK CLOTH 6.3 OZ
61978	633	INSULATION FOAM POLYURETHANE PDL2207
61979	698	LAMIN EPOXY/GLASS PC BOARD
61980		DELETED SEE 62016
61981	548	FILM POLYCHROME/POLYESTER
61982	719	LAMIN URALANE 5570 COATED WITH FC721
61983	672	LACING TAPE AIR-TEX 17
61984	1,344	RUBBER SILICONE RTV 2318
61985	1,327	RUBBER SILICONE 89780
61986		DELETED SEE 61969
61987	381	COATING RC9108 4334-112 WHITE
61988		DELETED SEE 05574
61989		DELETED SEE 20371
61990		DELETED SEE 05251
61991		DELETED SEE 06475
61992	512	FASTENER VELCRO NOMEX HI-AIR HAQ 12-2-200-SAI LOOP AND 12-1-200 HOOK
61993	59	ADHESIVE C9-4215/H3561 EPOXY
61994	485	FABRIC NYLON/PVC HERCULITE 20
61995	692	LAMIN EPOXY/GLASS AEROLAM 110
61996	496	FABRIC SILICONE/GLASS 3010
61997	392	COATING URETHANE 17875-5008 WHITE
61998	1,307	RUBBER NITRILE 160
61999	1,447	TAPE SCOTCH 474
62000	1,329	RUBBER SILICONE CHOSEAL 1285
62001	1,266	REGULATOR OXYGEN
62002	1,362	RUBBER SILICONE SR200
62003	645	INSULATION FOAM TEXTHANE 220-20 URETHANE
62004	347	COATING EPOXY 18 SERIES CONDUCTIV
62005	1,344	RUBBER SILICONE RTV 30-121
62006	1,341	RUBBER SILICONE RTV 103
62007	623	INSULATION FOAM OMAR100 POLYURETHANE
62008	401	COMPOUND THERMACOTE POLYBUTENE
62009	401	COMPOUND THERMACOTE PINK
62010	694	LAMIN EPOXY/GLASS E720
62011	1,517	WEBBING NMX/HOOK HAQ-12-1-100
62012	755	LUBE OIL QUAKER STATE 90
62013		DELETED SEE 05949
62014	1,442	TAPE PS ADHESIVE
62015		DELETED SEE 06232
62016	291	CABLE ELEC CAMERA/PVC INSULATION
62017	669	LABEL MARKING RC 55 PAPER
62018		DELETED SEE 05411
62019	1,445	TAPE SCOTCH 380 COTTON
62020	404	CONFIGURATION NOMEX/RTV
62021	442	FABRIC COTTON FR/POLYETHYLENE LINING
62022	581	HOSE WAVA SILICONE/NOMEX
62023	479	FABRIC NOMEX/TEF FILM/NOMEXWEB
62024		DELETED SEE 61149
62025	414	CONTAINER FOOD NYLON
62026	650	INSULATION FOAM URETHANE/PS ADHES
62027	306	CLIPS CORD B2

MSFC-HDBK-527 REV F 9999942 0006720 7

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
62028	717	LAMIN SCOTCHPLY 1009-36 EPOXY
62029	709	LAMIN FM5055 CARBON PHENOLIC
62030	1,360	RUBBER SILICONE SE5549
62031	1,360	RUBBER SILICONE SE5559
62032		DELETED SEE 61846
62033	1,262	POTTING COMPOUND TRIDOX F88 EPOXY
62034	577	HOSE PLASTIC/SILICONE RUBBER
62035	450	FABRIC ELASTIC 733 1.25 WIDE
62036	450	FABRIC ELASTIC 1700 1.0 WIDE
62037	464	FABRIC KEVLAR U 2209
62038	389	COATING SYNKOTE 71976 BLUE
62039	1,392	SEALANT RUBBER 27980
62040	1,252	POTTING COMPOUND EPOXY PUTTY 3249 A/B
62041	1,478	THREAD NYLON SIZE E OLIVE DRAB
62042	442	FABRIC COTTON RED
62043		DELETED SEE 06516
62044	644	INSULATION FOAM STYRENE
62045	863	PLASTIC DKE450/ACRYLIC PVC
62046	686	LAMIN CE9020/120/45% RC
62047	694	LAMIN EPOXY/GLASS CE9020/KEVLAR 49
62048	787	PAPER DRY-SILVER TYPE 7771
62049	408	CONNECTOR ELECT SILICONE RUBBER/CERAMIC
62050		DELETED SEE 61527
62051	679	LACING TAPE NOMEX/VITON
62052	580	HOSE TFE/CARBON FILLED
62053	1,467	TAPE/DISPENSER VINYL/PVAC
62054		DELETED SEE 05407
62055	705	LAMIN EPOXY/KEVLAR DSX501/181 KEVLAR 49
62056	720	LAMIN/EPOXY/KEVLAR E720FR/KEVLAR 49-181
62057		DELETED SEE 62819
62058		DELETED SEE 05414
62059	308	COATING 03-GY-62 POLYURETHANE FLAT LIGHT GRAY
62060	307	COATING 03-BK-29 POLYURETHANE FLAT BLACK
62061		DELETED SEE 05404
62062	375	COATING POLYURETHANE YELLOW/SUPER KOROPON
62063		DELETED SEE 06047
62064	361	COATING LATEX 3715-24-1 A/B TC
62065	361	COATING LATEX 3715-16-1 A/B EPOXY
62066	1,290	RUBBER FLUOROELASTOMER O-RING
62068	668	LABEL IDENTIFICATION PVC/CLOTH STREAMER
62069	1,268	ROD REINFORCED GRAPHITE/PHENOLIC
62070	686	LAMIN CARBON/PHENOLIC 2267-01
62071		DELETED SEE 05131
62072	573	HOSE FLEX PTFE/CARBON FILLED
62073	1,385	SCREEN POLYESTER/PVC COATED MESH
62074	445	FABRIC DACRON 15453 7.52 OZ/YD
62075	381	COATING PYROCOAT 565 (INORGANIC)
62076	1,258	POTTING COMPOUND STYCAST 2641-40/C9
62077	89	ADHESIVE DENSIL/KAPTON
62078	210	ADHESIVE PERMACEL KAPTON
62079	128	ADHESIVE EPIPHEN 825A EPOXY
62080	1,304	RUBBER NEOPRENE NS111B
62081		DELETED SEE 06176
62082	71	ADHESIVE CHEMLOK AP131
62083	766	MOLD COMPOUND EPOXY-DRY EPOX/POLYES
62084		DELETED SEE 05283
62085	1,433	TAPE NELTAPE 100 TRANSFER
62086	655	INSULATION POLYSTYRENE/FLUOREL
62087	524	FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 2899
62088	524	FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 2699
62089	524	FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 9999
62090	524	FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 0199
62091	524	FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 0399
62092	524	FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 1299
62093	511	FASTENER VELCRO HOOK SJ3572 AND LOOP SJ3571
62094	411	CONNECTOR MS3112E14-19P
62095	1,043	PLASTIC PLASTAFLEX SCPP2500CB
62096	622	INSULATION FOAM NEOPRENE NOC
62097	390	COATING TUFF-HYDE TEFLON
62098	704	LAMIN EPOXY/GRAPHITE/KEVLAR
62099	717	LAMIN POLYIMIDE/RESIN X PLY
62100	512	FASTENER VELCRO NOMEX HI-AIR HAQ 12-1 HOOK AND HAQ 12-2 LOOP
62101	1,433	TAPE NELTAPE 410 TRANSFER
62102	471	FABRIC NOMEX 7878/POLYESTER954
62103	773	MOLD COMPOUND URETHANE VL422M2
62104	353	COATING GAGEKOTE 8
62105	686	LAMIN CARBON/PHENOLIC 2269-01
62106		DELETED SEE 62070
62107	313	COATING 4699-121A/4334-109
62108	445	FABRIC DACRON FELT
62109	225	ADHESIVE PRESSURE SENSITIVE
62110	957	PLASTIC LEXAN 940 POLYCARBONATE
62111	959	PLASTIC LEXAN GF3000 POLYCARBONATE
62112	1,512	VYDAX AR FLUOROCARBON
62113	1,404	SPONGE RUBBER ENSOLITE AL PVC/NITRILE
62114	612	INSULATION FOAM CPR9700-1.75XF POLYURETHANE
62115	612	INSULATION FOAM CPR9700-1.45S POLYURETHANE
62116	612	INSULATION FOAM CPR9700-20 POLYURETHANE
62117	635	INSULATION FOAM POLYURETHANE/POLYESTER 3013
62118	763	MOLD COMPOUND DAP DC-62
62119		DELETED SEE 60663
62120		DELETED SEE 61764
62121	1,402	SOCKS COTTON TUBE
62122		DELETED SEE 20448
62124		DELETED SEE 05584
62126	1,518	WEBBING NOMEX TAPE
62127	1,476	THREAD NOMEX
62128		DELETED SEE 60728
62129		DELETED SEE 05128
62130	345	COATING ECCOCOAT EC D35
62132	772	MOLD COMPOUND PROFAX 7231
62133	1,278	RUBBER COHRLASTIC 9235
62134	314	COATING 515-700/910-704 463-3-100/118

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006721 9

MATCD	PAGE	DESIGNATION
62135	313	COATING 513-703/821-331/910-736
62136		DELETED SEE 20528
62137	753	LUBE OIL HALOCARBON MO-10
62138	165	ADHESIVE FILM FM300 EPOXY
62139	169	ADHESIVE FOAM FM41
62140	1,267	RESIN RC2 IMPREGNATING
62141	547	FILM PHOTOGRAPHIC EN4
62142	655	INSULATION PYRALUX POLYIMIDE
62143	1,304	RUBBER NEOPRENE NS111
62144	395	COATING XECOTE
62145	688	LAMIN EPOCAST 31/9216/1581 CLOTH
62147	1,374	RUBBER VITON CPD 68514A
62148	184	ADHESIVE LOCTITE 290
62149	187	ADHESIVE LOCTITE 80477
62150	1,269	ROD TEFLON/25% GLASS
62151	1,514	WEBBING DACRON 1250LB
62152	1,515	WEBBING DACRON 300LB
62153	415	CORD DACRON 3
62154	1,395	SEALANT TEFLON TFE O-RING
62155	444	FABRIC COTTON/DACRON
62156	433	FABRIC 100% COTTON FR 7 OZ BLUE
62157	155	ADHESIVE EPOXY XA924-40/E793
62158		DELETED SEE 60430
62159	612	INSULATION FOAM CPR9700-1.75 POLYURETHANE
62160	1,349	RUBBER SILICONE RTV 577
62161	1,260	POTTING COMPOUND STYCAST 2850GT/24LV
62162	656	INSULATION SMRD 100F90
62163	656	INSULATION SMRD 100F90/FR 7
62164	656	INSULATION SMRD 100F90/FR 13
62166		DELETED SEE 61926
62167	1,289	RUBBER FLUOREL V23
62168	1,487	TUBING FLUOREL 50FC009
62169	620	INSULATION FOAM MINICELL L200/FLUOREL
62170	647	INSULATION FOAM URETH KUA100/FLUOREL COATED
62171	186	ADHESIVE LOCTITE 80426
62172	186	ADHESIVE LOCTITE 80418
62173	252	ADHESIVE SPEEDBONDER 324/CA707
62174	1,414	TAPE CASSETTE 10635183 D3
62175	620	INSULATION FOAM MINICELL L200/AL 5052H32
62176	712	LAMIN LEXAN/TEDLAR
62177	1,394	SEALANT TEFLON NOC
62178	185	ADHESIVE LOCTITE 493
62179	185	ADHESIVE LOCTITE 495
62180	185	ADHESIVE LOCTITE 515
62181	186	ADHESIVE LOCTITE 80092 SUPERGLUE
62182	186	ADHESIVE LOCTITE 80414 LOCKNUTS
62183	350	COATING EPOXY/POLYAMIDE
62184	1,365	RUBBER SUCTION CUP
62185	774	MOLD COMPOUND VALOX 420 SEO
62186	772	MOLD COMPOUND PROFAX SE-012
62188	1,327	RUBBER SILICONE 6017 HI DAMP
62189	425	DENTURE ACRYLIC ACRA-WELD T2C1
62190	414	CONNECTOR SILICONE
62191	412	CONNECTOR P/N 41203 PHENOLIC
62192	361	COATING LATEX 3715-25-2 A/B
62193	394	COATING WONDER/PRIMER 442-3B
62194		DELETED SEE 05301
62195	1,396	SEALANT TRIBOLON PI101 POLYIMIDE
62196	586	INK DRY 9200/JCP E20 PAPER
62197	586	INK DRY 9200/JCP K10 PAPER
62198	353	COATING GREY ENAMEL/PRIMER
62199	708	LAMIN F164/181 KEVLAR-49
62200	439	FABRIC CERAMIC FELT
62201	1,381	RUBBER VITON V747-7
62202	393	COATING VARNISH GLPT RED
62203	1,272	RUBBER BUTYL
62204		DELETED SEE 00367
62205	520	FASTENER VELCRO NYLON LOOP 2000 PS 0104
62206		DELETED SEE 61777
62207	441	FABRIC COTTON DUCKWEAVE FR
62208	347	COATING EPOXY 3715-49-II A/B/C
62209	323	COATING ACRYLIC 3715-51-2B A-601
62210	323	COATING ACRYLIC 3715-52-1
62211	1,399	SHOE TENNIS NYLON/RUBBER
62212	427	DUCT E-720-E FR/120/MB0125-070
62213	536	FILM G402474 VAL/POLYIMIDE
62214	634	INSULATION FOAM POLYURETHANE STATHANE G502 SE
62215	301	CERAMIC DUROCK 204
62216	440	FABRIC COTTON 7 OZ/LINING 4 OZ FR
62217	554	FILM TEFLON TFE
62218	1,312	RUBBER PHENYL
62219	509	FASTENER VELCRO ASTRO LOOP 634 WITH BETA GLASS GROUND
62220	91	ADHESIVE DEVCON ST EPOXY
62221	154	ADHESIVE EPOXY PUTTY A/B
62222		DELETED SEE 61672
62223	1,453	TAPE SCOTCH 861 ALUMINUM WITH PRESSURE SENSITIVE ADHESIVE
62225	1,313	RUBBER PNF 270-003R ELASTOMER
62226	1,287	RUBBER FAIRPRENE SR554D
62227	478	FABRIC NOMEX/ARMALON BACKING
62228	479	FABRIC NOMEX/URETHANE COATED NYLON B
62229	478	FABRIC NOMEX WITH ZEPEL/ARMALON
62230	479	FABRIC NOMEX/ARMALON/URETHANE COATED NY
62231	478	FABRIC NOMEX WITH ZEPEL/ARMALON/URETHANE COATED NY
62232	151	ADHESIVE EPOXY EXTRA FAST SETTING
62233	839	PLASTIC CELANEX 3310
62234	406	CONNECTOR DAP/GLASS FILLED
62235	30	ADHESIVE AMSCO HOT MELT 112
62236	30	ADHESIVE AMSCO HOT MELT 233
62237	391	COATING URALANE 5753/CIRCUIT BRD
62238		DELETED SEE 20209
62239	713	LAMIN PHENOLIC 2210/A1100/1581
62240	151	ADHESIVE EPOXY FM300M
62241	1,396	SEALANT VANWAY FEP TEFLON O-RING
62242		DELETED SEE 62167
62243	236	ADHESIVE SCOTCHGRIP 1300
62244		DELETED SEE 00903
62245	454	FABRIC FYPRO
62246	454	FABRIC FYPRO 9805 P46EH

MSFC-HDBK-527 REV F 9999942 0006722 0

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
62247	1,266	RELEASE AGENT MS143
62248	1,266	RELEASE AGENT MS143/DYEPEN
62249	413	CONNECTOR SCOTCHFLEX SOCKET
62250	352	COATING FUSECOTE VE211-7A EPOXY
62251	250	ADHESIVE SILVER SILICONE
62252	1,443	TAPE PVF OT6
62253	649	INSULATION FOAM URETHANE/ARMALON/CSR300 ADHESIVE
62254	650	INSULATION FOAM URETHANE/BLACK VINYL COVER
62255	618	INSULATION FOAM KUA/ARMALON/CSR300 ADHES
62256	618	INSULATION FOAM KUA/BLACK VINYL COVER
62257	649	INSULATION FOAM URETHANE KUA
62258	294	CABLE INSULD/TEFLON 5481 TAPE
62259	294	CABLE INSULD/FES 51 REFL TAPE
62260	294	CABLE INSULD/ST8000X/FES 51
62261		DELETED SEE 60955
62262	587	INK DYNACURE LETTERING
62263	599	INSULATION ARMAFLEX RUBBER
62264	599	INSULATION ARMAFLEX/ARMSTRONG 520
62265	1,222	PLASTIC VALOX 730-1001 POLYESTER
62266	3	ACRYLIC CUVETTE 749 (BCS)
62267	1,416	TAPE EDGING 750 ACETATE PAPER WITH ADHESIVE
62268	959	PLASTIC LEXAN CHROMAFILTER LENS POLYCARBONATE
62269	313	COATING 513X332/910X457 PRIMER
62270	331	COATING CHEMGLAZE A571 RED/9924
62271	779	MULTI-LAYERED INSULATION MYLAR/ALUMINUM
62272	1,245	POTTING COMPOUND CASTALL 301/RT1
62273	153	ADHESIVE EPOXY PATCH KIT 907 GREEN
62274	698	LAMIN EPOXY/GLASS NEMA G11
62275	1,380	RUBBER VITON V14
62276	791	PAPER TELETYPE PRINTER
62277	788	PAPER FITCHBURG TIME MARK 30
62279	795	PENCIL SKILCRAFT MECHANICAL
62280	450	FABRIC FARRELL FIBERGLASS
62281	682	LACING TAPE SCOTCH
62282		DELETED SEE 05340
62283	402	COMPOUND THERMAL CONDUCTIVE URETHANE SMRD 902
62284	1,493	TUBING NYLON
62285	647	INSULATION FOAM TUFCOTE ACOUSTICAL
62286	647	INSULATION FOAM TUFCOTE ACOUSTICAL 104
62287		DELETED SEE 62357
62288	600	INSULATION BLANKET KAPTON/AL/MYLAR/DACRON
62289	575	HOSE LINER FLEX TFE/25% CARBON
62290	791	PAPER TELETYPEWRITER CARBON
62291	373	COATING POLYURETHANE PR1568 CONFORMAL
62292	613	INSULATION FOAM DENSITE 3
62293	613	INSULATION FOAM DENSITE 2
62294	627	INSULATION FOAM POLYIMIDE 1702
62295		DELETED SEE 06021
62296	2	ABSORBER ENERGY EAR 1002
62297	2	ABSORBER ENERGY EAR C2003/ADH
62298	420	CORD YALE 375 QUAD DACRON/KEV
62299	428	DUCTING RUBBER IMPREG COTTON
62300	951	PLASTIC KRATON 2701
62301	601	INSULATION BLANKET KAPTON/MYLAR/DACRON
62302	295	CABLE OSCILLOSCOPE
62303	291	CABLE EIM
62304	1,426	TAPE KAPTON/POLYIMIDE 583
62305	418	CORD NOMEX BRAIDED
62306	402	COMPOUND UNISET A316-7 EPOXY
62307	1,345	RUBBER SILICONE RTV 3112
62308		DELETED SEE 20710
62309	480	FABRIC NOR-FAB 400/8PT22
62310	341	COATING DCI SYSTEM 20 POLYMER
62311	626	INSULATION FOAM POLYESTER/PVC FLAME BOND
62312	1,365	RUBBER STOCKWELL 2023
62313	692	LAMIN EPOXY/GLASS CE3201
62314	1,275	RUBBER CHLOROPRENE VONAR 3
62315		DELETED SEE 61359
62317	1	ABLATIVE COMPOUND EPOXY PD451A
62318	566	GLOVE COMFORT NYLON/ACRYLIC
62319	1,260	POTTING COMPOUND STYCAST 2850KT/C11
62320	1,383	RUBBER VITON VD000B
62321	642	INSULATION FOAM SOLIMIDE FF201 POLYIMIDE
62322	643	INSULATION FOAM SOLIMIDE TA301 POLYIMIDE
62324	678	LACING TAPE NOMEX 1342G
62325	510	FASTENER VELCRO HOOK AND LOOP 1000 BACKING 0399
62326	450	FABRIC DURVIL/WOOL
62327	449	FABRIC DURVIL/NOMEX
62328	1,497	TUBING POLYOLEFIN TAT125 HST
62329	748	LUBE GREASE SILICONE G9042
62330	748	LUBE GREASE SILICONE G9052
62331	332	COATING CHEMGLAZE V021/9992
62332	333	COATING CHEMGLAZE V021/XYLENE
62333	333	COATING CHEMGLAZE V021/9995
62334	88	ADHESIVE DENNISON GLUE STIC
62335	1,479	THREAD POLYESTER LOFTEX T16
62336	566	GLOVE COMFORT NYLON/TRICOT
62337	721	LEATHER CHAP LIGHT WEIGHT
62338	787	PAPER DRY SILVER 7772
62339	155	ADHESIVE EPOXY T1401
62340	398	COMPOUND ACROSONIC 100 GEL
62341	19	ADHESIVE ABLEBOND 773-2 BRS
62343	68	ADHESIVE CERMALLOY T2100 EPOXY
62344	68	ADHESIVE CERMALLOY T2000 EPOXY
62345	223	ADHESIVE PR1546L
62346	752	LUBE OIL FRIQUIL V220 CELLUBE
62347	455	FABRIC GLASS/EPOXY L1040-108
62348	1,423	TAPE GLASS/SILICONE/ADHESIVE PE2347
62349	444	FABRIC COTTON/DCY JERSEY KNIT
62350	258	ADHESIVE THERMOGRIP 6368-15
62351	258	ADHESIVE THERMOGRIP 6363-15
62352	1,460	TAPE STICK AND STRIP 10470 SILICONE
62353	593	INK PILOT RAZOR POINT SW10PP
62354	434	FABRIC 520/S920 SILANE FINISH
62355	2	ABSORBER AFONIC VIBRASORB
62356	609	INSULATION FOAM CPR306-2/REFSET COATED
62357	600	INSULATION BLANKET KAPTON/DACRON/NOMEX
62358	1,415	TAPE CHARTPAK GRAPHIC 5017 GREEN
62359	637	INSULATION FOAM PYRELL WFP1406 CHARCOA
62360	443	FABRIC COTTON S55 F/P/VELCRO/NOMEX

MSFC-HDBK-527 REV F ■ 9999942 0006723 2 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
62361	476	FABRIC NOMEX TWILL 6.5 OZ
62362	461	FABRIC HT-90-40 NOMEX/STN RMVR
62363	774	MOLD COMPOUND VISILOX V201 A/B SIL
62364	670	LABEL TEMPILABEL 8D-210/99
62365	670	LABEL TEMPILABEL 4D-150/66
62366	1,449	TAPE SCOTCH 5491 SILICONE
62367	1,461	TAPE STRETCH SILICONE RUBBER
62368	540	FILM KODACOLOR VR/1000
62369	1,326	RUBBER SILICONE 4216A
62370		DELETED SEE 60056
62371	1,352	RUBBER SILICONE RTV 700
62372	366	COATING P527D/C527D/PRIMER
62373	312	COATING 463-12-8/PRIMER
62374	540	FILM KODAK 7294 HIGH SPEED
62375	697	LAMIN EPOXY/GLASS G10FR/SR240
62376	551	FILM RUCOTHANE CO-A769 POLYURETHANE
62377	1,448	TAPE SCOTCH 49
62378	1,414	TAPE CHARTPAK GRAPHIC 5005 ORANGE
62379	1,356	RUBBER SILICONE RTV SWSV81
62380	428	DUCT NEOPRENE IMPREG CTN FAB
62381	1,256	POTTING COMPOUND SCOTCHCAST 5 EPOXY
62382	392	COATING URETHANE MS470
62383	643	INSULATION FOAM STEPAN BX352M/DC3140 COATED
62384		DELETED SEE 61623
62385	1,298	RUBBER LATEX DENTAL DAM
62386	445	FABRIC COTTON/POLYESTER
62387		DELETED SEE 03046
62388	1,428	TAPE MEASURE ERWIN PC10
62389	387	COATING SOLAR ABSORBER ECP2200
62390	622	INSULATION FOAM NEOPRENE LS200
62391	347	COATING EPOXY 463-12-8/4593-30
62392	1,343	RUBBER SILICONE RTV 12 A/B
62393	1,363	RUBBER SILICONE TSC11
62394	1,455	TAPE SCOTCH Y9415 POLYESTER ACRYLIC ADHESIVE
62395	748	LUBE GREASE STOPCOCK SILICONE
62396	743	LUBE GREASE HIGH VACUUM SILICONE
62397	574	HOSE FLEX TEFLON/1% CARBON
62398	79	ADHESIVE CRACK 'N PEEL
62399	1,317	RUBBER RUCOTHANE 5225/MS122
62400	1,317	RUBBER RUCOTHANE 5154/MS122
62401	1,540	ZIPPER POLYESTER/DELRIN VFC 56
62402	1,273	RUBBER BUTYL B7764-11
62403	1,451	TAPE SCOTCH 635 POLYESTER
62404	1,441	TAPE POLYPENCO 2003 PTFE
62406	1,411	SYRINGE 60 CC POLYPROPYLENE/SILICONE
62407	151	ADHESIVE EPOXY FA8/BA5
62408	772	MOLD COMPOUND RYTON R-10
62409	773	MOLD COMPOUND RYTON R-7
62411	312	COATING 463-12-8/643-1-1 EPOXY
62412		DELETED SEE 60308
62413	409	CONNECTOR ELECTRICAL
62414	1,427	TAPE LETTERING 3M
62415		DELETED SEE 61358
62416	428	DUCT RUBBER
62417		DELETED SEE 61039
62418	566	GLOVE LATEX SOMAMED
62419	424	DECAL FOTOFOIL P
62420		DELETED SEE 62376
62421	584	INK CANON NP270F/JCP E20PAPER
62422	323	COATING ACRYLIC 90-10472 CORROSION PREVENTIVE
62423	1,407	SPONGE RUBBER SILICONE FOMEGA HT603
62424	652	INSULATION KAOWOOL CERAMIC/FOIL BACKING
62425	652	INSULATION KAOWOOL CERAMIC/SCRIM BK
62426	1,254	POTTING COMPOUND RTV 11/C9811
62427	1,254	POTTING COMPOUND RTV 11/C12
62428	348	COATING EPOXY 463-12-8/A276
62429	607	INSULATION FOAM CHEMLON 504 POLYIMIDE
62430	597	INK UNIMARK 960/JPC K10 PAPER
62431	686	LAMIN CARBON/CARBON REINFORCED
62432		DELETED SEE 06389
62433	700	LAMIN EPOXY/GLASS WITH EPOXYLITE 9653
62434	1,464	TAPE TEMP-R-TAPE G569
62435	776	MULTI-LAYERED INSULATION BLANKET
62436	413	CONNECTOR PLIERS UTICA 529
62437	578	HOSE SILICONE/PBI POS BREATHER
62438	576	HOSE NYLON/TEFLON R531-4
62439	335	COATING CHOCKFAST ORANGE PR610 TCF
62440		DELETED SEE 06555
62441	651	INSULATION FOAMGLAS CELLULAR
62442	650	INSULATION FOAM URETHANE/LT80/REFSET COATED
62443	588	INK KODAK 250/JCP E20 PAPER
62444	439	FABRIC CERAMIC AB312 WITH Z6070
62445	30	ADHESIVE AMICON XT1369 A/B
62446		DELETED SEE 05822
62447	229	ADHESIVE RE2039/H3537 EPOXY
62448	1,115	PLASTIC RYNITE 545
62449	132	ADHESIVE EPON 815 WITH EPOCAST HN951
62450	138	ADHESIVE EPON 828/EPOCAST HN951
62451	1,431	TAPE MYSTIK 7341 POLYESTER/ACRYLIC ADHESIVE
62453		DELETED SEE 05419
62454	1,284	RUBBER EPR MARVEL SEAL 1312
62456	350	COATING EPOXY/POLYAMIDE
62457	493	FABRIC RAYON GOAT HAIR
62458	397	COMPOSITE KEVLAR/EPOXY WRAP
62459	1,341	RUBBER SILICONE RTV 1/SILVER
62460	796	PIGMENT GREEN GLOVE BLADDER
62461	290	CABLE COAX RG142 PTFE CORE FEP JACKET SILVER COATED COPPER
62462	1,439	TAPE P551B SILICONE
62463	505	FASTENER PLASTIC BOOK BINDER
62464	1,505	TUFFAK POLYCARBONATE F1
62465		DELETED SEE 60751
62468	1,095	PLASTIC RCAS 2400/ANTISTATIC 2 MIL THICK ROLLED INTO TUBULAR SHAPE
62469	504	FASTENER KYNAR MK 7201
62470	669	LABEL NOMEX/RAYON
62471		DELETED SEE 61114
62472	1,398	SHIELD POLYCARBONATE PLASTIC
62473	785	PACKAGE FOOD SARAN/POLYETHYLEN
62474	1,513	WARMER FOOD NEMA G-11 EPOXY/GL

MSFC-HDBK-527 REV F 9999942 0006724 4

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
62476	1,411	SUCTION CUP RUBBER STILSON4037
62477	691	LAMIN EPOXY/GLASS
62478	578	HOSE REDAR A11200 SILICONE/PBI
62479	1,282	RUBBER EPDM 12045-01
62480	550	FILM RISTON 730FR
62481	706	LAMIN EPOXY/KEVLAR E719/12 KEVLAR 181
62482	705	LAMIN EPOXY/KEVLAR CE306/281
62483		DELETED SEE 62386
62484	1,430	TAPE MYLAR/POLYESTER PS
62485	711	LAMIN KEVLAR 143/E788
62486	415	CORD CELION 6000 EPOXY/CARBON
62487		DELETED SEE 62126
62488	1,519	WEBBING NYLON 300 LB
62489	285	BELT POLYFLEX 8C84C077 COTTON/POLYESTER
62490		DELETED SEE 60863
62491	388	COATING SOLITHANE C113-300/DC3140
62492	472	FABRIC NOMEX 98379
62493	446	FABRIC DACRON WITH RUBBER BUTYL
62494	564	GASKET SILICONE/MONEL
62495	1,531	WIRE ELEC RAYCHEM 55 ETFE
62496		DELETED SEE 20877
62497		DELETED SEE 20877
62498	1,531	WIRE ELEC RAYCHEM 44 WITH FEP TUBING
62499	1,531	WIRE ELEC RAYCHEM 44 WITH ATLAS TUBE
62500		DELETED SEE 05236
62501		DELETED SEE 62591
62502	537	FILM GORTEX LAMIN WITH FABRIC NOMEX
62503	553	FILM TEFLON GORTEX
62504	660	KEL-F 6061-T6 10% GLASS
62505	1,470	TEFLON PTFE MULTIFILL 427
62506	1,473	TEFLON TFE/30% GLASS
62508	572	HEATER STRIP/KAPTON 24 AWG
62509	571	HEATER STRIP HK607005A 24AWG
62510	1,531	WIRE ELEC RAYCHEM 44/KAPTON
62511		DELETED SEE 62517
62512	1,534	WIRE ELEC WITH METAL BRAID SHIELD
62513	1,523	WIRE ELEC CU/MYLAR/MYLARWRAP
62514	1,534	WIRE ELEC WITH FIBERGLASS SLEEVE
62516		DELETED SEE 05275
62517	1,524	WIRE ELEC ETFE TEFZEL
62518	1,524	WIRE ELEC ETFE WHT 20 AWG
62519		DELETED SEE 62517
62520		DELETED SEE 05236
62521		DELETED SEE 62517
62522	1,526	WIRE ELEC FEP/POLYIMIDE TAPE
62523		DELETED SEE 05449
62524	1,528	WIRE ELEC PEEK (POLYETHER-ETHERKETONE)
62525	1,524	WIRE ELEC E050A040
62526		DELETED SEE 62524
62527	1,534	WIRE ELEC VARGLAS SLEEVE
62528	1,523	WIRE ELEC 2-WIRE CABLE
62529	1,526	WIRE ELEC HEADSET 28 AWG
62530		DELETED SEE 20756
62531	570	HARNESS AND CONNECTOR 26 AWG
62532	1,529	WIRE ELEC POLYURETHANE 8771
62533	570	HARNESS ASSEMBLY NOMEX BRAIDED 200 DENIER COVER
62534	409	CONNECTOR ELECTRICAL
62535	623	INSULATION FOAM OMALON 1 FR/ACOUSTFAB LINER
62536	623	INSULATION FOAM OMALON 1 POLYURETHANE FR
62537	768	MOLD COMPOUND GLASKYD 2051B GL/ALKD
62538	169	ADHESIVE FOAM POLYURETHANE
62539	674	LACING TAPE GUDE-LACE
62540	595	INK SCREEN DAYGLO SUPER 67
62541	1,448	TAPE SCOTCH 53 POLYURETHANE/SOLITHANE 113/300
62542	89	ADHESIVE DENSIL SILICONE PS
62543	252	ADHESIVE SPRAY 74
62544	1,513	WASH CLOTHS BABY UNSCENTED
62545	451	FABRIC FELT DURETTE BATTING
62546	1,477	THREAD NOMEX
62548	503	FABRIC ZIRCONIUM TREATED WOOL
62549	705	LAMIN EPOXY/KEVLAR DUCT
62550	297	CAPLUGS PVC EC22 CANNON 500
62551	541	FILM KYNAR NATURAL
62552	1,503	TUBING THERMOFIT VITON HST
62553	575	HOSE LINER PTFE
62554	733	LUBE DRY MOLYKOTE G-N
62555	745	LUBE GREASE KRYTOX 240AZ
62556	1,333	RUBBER SILICONE D173-100-12
62557	148	ADHESIVE EPOXY 11
62558	314	COATING 515-703/910-736 PRIMER
62559	711	LAMIN KEVLAR 49/SKYBOND 703
62560	711	LAMIN KEVLAR 49/32 EPOXY
62561	653	INSULATION LAMINATE MARQUISETTE
62562	1,372	RUBBER VITON A 3-920
62563		DELETED SEE 62275
62564	1,372	RUBBER VITON A 017-ESQ
62565		DELETED SEE 05179
62566		DELETED SEE 05179
62567		DELETED SEE 05179
62568		DELETED SEE 05179
62569		DELETED SEE 05179
62570		DELETED SEE 05179
62571		DELETED SEE 05275
62572		DELETED SEE 05275
62573		DELETED SEE 05275
62574	1,530	WIRE ELEC PYRAD 1000
62575	1,532	WIRE ELEC SILICONE RUBBER 20 AWG
62576		DELETED SEE 20756
62577		DELETED SEE 05449
62578		DELETED SEE 05236
62579		DELETED SEE 62510
62580		DELETED SEE 62510
62581		DELETED SEE 62514
62582	1,534	WIRE ELEC VARGLASS SLEEVE 20AWG
62583		DELETED SEE 60651
62584	290	CABLE COAXIAL 26 AWG
62585		DELETED SEE 62499
62586		DELETED SEE 05236
62587		DELETED SEE 62591
62588		DELETED SEE 62591

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006725 6 ■

MATCD	PAGE	DESIGNATION
62589	1,526	WIRE ELEC FEP/POLYIMIDE TAPE
62590		DELETED SEE 62591
62591	1,526	WIRE ELEC FEP/POLYIMIDE TAPE
62592		DELETED SEE 62495
62593		DELETED SEE 62495
62594		DELETED SEE 20877
62595		DELETED SEE 20877
62596		DELETED SEE 20877
62598	1,531	WIRE ELEC RAYCHEM 44 SHIELD/INSULATION
62599	1,534	WIRE ELEC URETHANE 29 AWG
62702		DELETED SEE 06475
62703	776	MULTI-LAYERED INSULATION ALUMINIZED FIBERGLASS/FEP TEFLON TAPE/SILVER/INCONEL/POLYESTER
62704	543	FILM MYLAR 315 LTYEEL/JCP E20
62705	1,434	TAPE NOMEX UTILITY FR PS ADHESIVE
62706	410	CONNECTOR ELECTRICAL 97E
62707		DELETED SEE 20891
62708	709	LAMIN FORTIN CORE 2222
62709	485	FABRIC NYLON/URETHANE 1111 COATED
62710		DELETED SEE 61820
62711		DELETED SEE 61820
62712	551	FILM SAN
62713	1	ABLATOR MTA-3 TROWELLABLE
62714	1	ABLATOR MSA-2 SPRAYABLE
62715	4	ADAPTER CONNECTOR KYNAR/SS
62716	24	ADHESIVE ADCAM 760
62717	41	ADHESIVE ARMSTRONG A3
62718	103	ADHESIVE EA9330 EPOXY
62719		DELETED SEE 60425
62720	69	ADHESIVE CHEMLOK 234B
62721	135	ADHESIVE EPON 828 EPOXY
62722		DELETED SEE 00007
62723	182	ADHESIVE LEFKOWELD 46/52 EPOXY
62724		DELETED SEE 05758
62725	266	ADHESIVE TRUCAST 111M/901 EPOXY
62728	282	BAG MINIGRIP POLYETHYLENE
62729	282	BAG NYLON MESH X-1591
62730	287	BRAID ELASTIC NYLON/RUBBER
62732	421	CORE ASSEMBLY 7U82634
62733	530	FILA WOUND CASE COMP/SEALER
62734	531	FILA WOUND CASE COMPONENTS
62735	647	INSULATION FOAM TUNNEL/ALBICOTE
62736	666	LABEL IDENTIFICATION
62737		DELETED SEE 05275
62739	296	CABLE TIES TY-27M NYLON
62740	296	CABLE TIES TY-28M NYLON
62741	295	CABLE TIES PAN-TY HALAR
62742	296	CABLE TIES PAN-TY TEFZEL
62743	303	CIRCUIT BREAKER HEINEMAN
62744	305	CLAMP RL5033/CUSHION L32171
62745	305	CLAMP ST253/CUSH MOSITES 1059
62746	304	CLAMP NYLON
62747	306	CLAMP TA02112 WITH INSUL
62748	397	COMPOSITE NEOPRENE/NOMEX HT337
62749	397	COMPOSITE NEOPRENE/POLYESTER
62750	398	COMPOSITE VITON B50/DACRON
62751	398	COMPOSITE VITON B50/NOMEX 426
62752	398	COMPOSITE VITON B50/NOMEX RF41
62753	398	COMPOSITE VITON/POLYEST DY793
62754	398	COMPOSITE VITON B50/POLYESTER
62755	403	CONFIG PWB/COATED WITH PR1568
62756	415	CORD BUNGEE 3862T17
62757	417	CORD KEVLAR POLYURETHANE COATED
62758	422	CORK B-STAGED/COATING TURCO T6109
62759	422	CORK P50/ADHESIVE RTV 560
62760	422	CORK P50/COATING FRL-3
62761	422	CORK P50/COATING 051-A69
62762	422	CORK P50/COATING TURCO T6109
62763	422	CORK/HYPALON HFR2200
62764	423	CORK/HYPALON HFR2200/ACTIVATOR
62765	332	COATING CHEMGLAZE II A276/9922 PRIMER
62766	307	COATING 023-GW-3/CHEMGLAZE A276 P
62767	349	COATING EPOXY POLYAMIDE GRAY
62768	350	COATING EPOXY WHITE ON .020" AL
62769	356	COATING HYPALON HFR2200 WHITE
62770	357	COATING INORGANIC WHITE
62771	363	COATING MXSA
62772	363	COATING MXSA/TURCO T6109/AL(OH)3
62773	364	COATING MXSA/TURCO T6109/MG(OH)2
62774	364	COATING MXSA/TURCO T6109/OXALIC
62775	364	COATING MXSA/TURCOT6109/HYP H2200
62776	373	COATING POLYURETHANE PR1060D
62777	374	COATING POLYURETHANE PR1568M
62778	315	COATING 550/5007/FOAM 658 POLYURETHANE
62779	390	COATING TRAIL CHEM PRIMER 20464-66
62780	375	COATING PR855 SEMCO
62781	386	COATING SILICONE PV100 WHITE
62782	390	COATING TURCO T6094 BLACK
62783	392	COATING URETHANE 550/5007 BASE
62784	393	COATING VITON/CLAY ON FAB NYLON
62785	393	COATING VITON B50/ZIPPER NOMEX
62786	312	COATING 463-3-209 EPOXY
62787	424	DAMPER VIBRATION VHDS 33 DIDC
62788	650	INSULATION FOAM WITCO 658 FUTURA 5007/550
62789	572	HOSE AIR DUCT FLEXFLYTE L1
62790	573	HOSE AIR DUCT FLEXFLYTE L9
62791	428	DUCT SILICONE IMPREG 5276K22
62792	437	FABRIC BALLISTIC NYLON/VITON
62793	438	FABRIC BETA GLASS/TFE NOC
62794	438	FABRIC BETA/REFSET COATED
62795	439	FABRIC CARBON PHENOLIC ABLATIVE
62796	446	FABRIC DACRON S1185
62797	446	FABRIC DACRON S1185/FORM A
62798	446	FABRIC DACRON S1185/FORM B
62799	446	FABRIC DACRON S1185/FORM C
62800	509	FASTENER VELCRO HI-AIR HOOK 65 WITH PS 0372
62801	455	FABRIC GLASS/POLYESTER F149 IMPREG
62802	464	FABRIC KEVLAR RF443/TAPE RF282
62803	462	FABRIC KEVLAR 1813-2 WITH VITON
62804	463	FABRIC KEVLAR 29/774

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
62805	463	FABRIC KEVLAR 29/H7000-605
62806	463	FABRIC KEVLAR 49 STYLE 26435
62807	464	FABRIC KEVLAR 9M03893/1813
62808	465	FABRIC KEVLAR/NYLON
62809	473	FABRIC NOMEX C4270
62810	473	FABRIC NOMEX GAC-RF-444
62811	475	FABRIC NOMEX RF444/TAPE RF282
62812	484	FABRIC NYLON/ACHESON +500
62813	484	FABRIC NYLON/DYNATHERM D65
62814	379	COATING PRIMER/ENAMEL TFE
62815	379	COATING PRIMER TFE TEST DISCS
62816	530	FIBER OPTICS SENSOR PROBE
62817	757	MARKER ELECTROLYTE MSC4
62818	306	CLEANER FORMULA APC
62819	1,500	TUBING TEFLON FEP HST
62820	1,498	TUBING PTFE NON-HEAT SHRINK
62821	792	PASTE SILVER SOLDER
62822		DELETED SEE 61407
62823	305	CLAMP SLEEVE TEFLON TFE
62824	753	LUBE OIL HALOCARBON 11-14
62825	320	COATING 851-255 BLACK/850-204 TFE
62826	1,389	SEALANT GS1450 POURABLE
62827		DELETED SEE 62820
62828		DELETED SEE 62903
62830		DELETED SEE 62820
62831	743	LUBE GREASE HALOCARBON 25-5S
62832		DELETED SEE 61407
62833	720	LEAK DETECTOR SHERLOCK 5 SEC
62834		DELETED SEE 60442
62835	559	FLUOROGRAY 5330-LNO-2638X
62836		DELETED SEE 62835
62837		DELETED SEE 06088
62838	559	FLUOROGRAY 5330-084-1774
62839		DELETED SEE 06088
62840	559	FLUOROGRAY 5330-LNO-2628X
62841		DELETED SEE 60375
62842		DELETED SEE 06088
62844		DELETED SEE 05275
62845		DELETED SEE 05275
62846	1,364	RUBBER SILICONE/ALUMINUM/DC282
62847	1,468	TEFLON 55L2 SEALS
62848	1,469	TEFLON G-83 TFE
62849		DELETED SEE 60467
62850	650	INSULATION FOAM WIPES MICRO-CLEAN POLYURETHANE
62851	673	LACING TAPE F416 TEFLON COATED
62852	1,468	TEFLON COATED SLUGS
62853		DELETED SEE 63491
62854	1,268	ROD CHEMFLUOR TFE VIRGIN EXT
62855	1,504	TUBING VIRGIN FEP TEFLON
62856	1,377	RUBBER VITON O-RING
62857	292	CABLE ELEC RTM437 CU IMBEDDED IN FEP WITH TEFLON OVERWRAP
62858		DELETED SEE 62851
62859		DELETED SEE 05417
62860	1,498	TUBING PTFE HST
62861		DELETED SEE 61407
62862	1,485	TUBING FEP 100 HST
62863	382	COATING REFSET RL4389
62864		DELETED SEE 61274
62865		DELETED SEE 61132
62866		DELETED SEE 63491
62867		DELETED SEE 61407
62868		DELETED SEE 05451
62869		DELETED SEE 05275
62870	281	ARMALON
62871		DELETED SEE 06088
62872	1,380	RUBBER VITON V709-9
62873	1,372	RUBBER VITON A
62874		DELETED SEE 62201
62875		DELETED SEE 05275
62876	400	COMPOUND LEAK TEST MMSY824C100
62877		DELETED SEE 62553
62878	737	LUBE FLUOROLUBE GRADE FS5
62879	1,294	RUBBER KALREZ 1004
62880	1,524	WIRE ELEC E7371001
62881	796	PENETRANT I-319
62882	426	DEVELOPER D90
62883	1,442	TAPE PTFE SEALANT 48
62884	1,523	WIRE ELEC
62885	682	LACING TAPE PTFE ENAMELED
62886	400	COMPOUND LEAK TEST N727C
62887		DELETED SEE 62820
62888		DELETED SEE 62823
62889	351	COATING FEP
62890		DELETED SEE 05275
62891	532	FILM ACLAR 933A
62894		DELETED SEE 05451
62895	297	CARBON P9
62896	1,267	RESIN R2
62897	319	COATING 850-204/855-225 TFE
62898	796	PENETRANT FLUORESCENT P6F-4L
62899	796	PENETRANT FLUORESCENT P6F-4LNC
62900	426	DEVELOPER NQ-1
62901	426	DEVELOPER D-1
62902	1,470	TEFLON TFE 3602
62903	1,498	TUBING PTFE SHRINKABLE
62904		DELETED SEE 61407
62905		DELETED SEE 62819
62906		DELETED SEE 62819
62907	575	HOSE LINER TEFLON CONDUCTIVE
62908	1,295	RUBBER KALREZ 1046R2
62909	1,295	RUBBER KALREZ 1046R2M
62910		DELETED SEE 05275
62911	1,386	SEALANT DIRECT SHAFT CARBON G84
62912	1,386	SEALANT CIRCLE P/N 32834
62913	795	PENETRANT FLUORESCENT P6F-4
62914		DELETED SEE 62763
62915	484	FABRIC NYLON/FLUOROLUBE OIL
62916	484	FABRIC NYLON/KEL-F 90 GREASE
62917	485	FABRIC NYLON/VITON

MSFC-HDBK-527 REV F 9999942 0006727 T

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
62918	486	FABRIC NYLON/VITON/ACHESON+500
62919	486	FABRIC NYLON/VITON/FLUOREL
62920	487	FABRIC PAN 2700-40
62921	491	FABRIC POLYESTER RF415
62922	494	FABRIC RIPSTOCK NYLON/VINYL COATED
62923	496	FABRIC SILICONE 1 GLASS
62924	433	FABRIC 46% COTTON/POLYESTER/LYCRA
62925	527	FEEDTHRU CONNECTOR KYNAR/SS
62926	530	FELT UL94HBF/C430 ADHESIVE BACK
62927	530	FIBERGLASS ON FILM ALUM/TEDLAR
62928	531	FILLER CORFIL 615 EPOXY
62929	533	FILM CAPRAN 980 NYLON
62930	544	FILM NM50-13 KAPTON/NOMEX
62931	540	FILM KODAK PCF135-36 STYLE2483
62932	450	FABRIC FACILON 1814 PVC BLUE
62933	451	FABRIC FIBERGLASS 1450-045
62934	546	FILM PANATONIC X/ACETATE
62935	546	FILM PANATONIC X3400/ESTAR
62936	550	FILM POLYURETHANE/CARBON LH86-13
62937	553	FILM TEDLAR PVF 150 BLACK 30CC
62938	552	FILM TEDLAR 400 BS 30 WHITE
62939	557	FLEX ELEMENT S/N-4
62940	603	INSULATION FOAM ABLESTICK/ECCOSPHERES S1
62941	603	INSULATION FOAM ALBICOTE
62942	603	INSULATION FOAM ALBICOTE FRL 3A
62943	437	FABRIC ARGNAMITE GRAPHITE COATED
62944	452	FABRIC FLAME RETARDANT
62945	460	FABRIC HT-337 NOMEX
62946	603	INSULATION FOAM ALBI-COTE FRL 5A
62947	604	INSULATION FOAM BX250
62948	605	INSULATION FOAM BX250/COATING V555 VINYL
62949	605	INSULATION FOAM BX250/COATING RL3788
62950	604	INSULATION FOAM BX250 COATED WITH D65
62951	604	INSULATION FOAM BX250 FRL COATED
62952	604	INSULATION FOAM BX250 WITH TI02 FILLER
62953	605	INSULATION FOAM BX250/FRL COATED/DMS0 GEL
62954	393	COATING URETHANE ON 1/16 AL FOIL
62955	624	INSULATION FOAM PDL4034 UNCOATED/MACHINED/IMBEDDED IN SHELL OF BX250
62956	607	INSULATION FOAM CHEMPOL/SOLITHANE 113/300
62957	608	INSULATION FOAM COOK YELLOW/GREEN
62958	608	INSULATION FOAM COOK GREEN 977-G-325 SPRAY-ON
62959	611	INSULATION FOAM CPR920-9-2/HFR2200 PS
62960	609	INSULATION FOAM CPR488
62961	609	INSULATION FOAM CPR488 CONDENSATE
62962		DELETED SEE 62961
62963	610	INSULATION FOAM CPR488/ECCOBOND 59K ADHES
62964	610	INSULATION FOAM CPR488/ECCOBOND 60L ADHES
62965	610	INSULATION FOAM CPR488/ED199 COATED
62966	610	INSULATION FOAM CPR488/FRL COATED/DMS0 GEL
62967	610	INSULATION FOAM CPR488/FRL COATED/E GLYCOL
62968	610	INSULATION FOAM CPR488/FRL3 COATED
62969	610	INSULATION FOAM CPR488/FRL3 COATED/EMULSION
62970	611	INSULATION FOAM CPR488/FRL3 TY2 COATED
62971	610	INSULATION FOAM CPR488/FRL3 3193 TY2 COATED
62972	610	INSULATION FOAM CPR488/FRL3 AND PERSERVO COATED
62973	609	INSULATION FOAM CPR488 NET SPRAY
62974	611	INSULATION FOAM CPR488/TANCO 9708 COATED
62975	609	INSULATION FOAM CPR488/22592 BLACK CARBON FILLED CONDUCTIVE COATING
62976	611	INSULATION FOAM CPR50
62977	611	INSULATION FOAM CPR50A
62978	612	INSULATION FOAM CPRTC263-93
62979	613	INSULATION FOAM CREST 2460
62980	614	INSULATION FOAM ECCOFOAM 12-2H
62981	614	INSULATION FOAM ECCOFOAM 12-6H
62982	616	INSULATION FOAM ET-TPS
62983	608	INSULATION FOAM CPR1061 FR
62984	646	INSULATION FOAM TSR336-2 FR
62985	646	INSULATION FOAM TSR336-3 FR
62986	646	INSULATION FOAM TSR336-4 FR
62987	646	INSULATION FOAM TSR 3365 FR
62988		DELETED SEE 60389
62989	616	INSULATION FOAM GREAT STUFF 1/2/3
62990	627	INSULATION FOAM POLYETHYLENE FLEXIBLE
62991	617	INSULATION FOAM GREAT STUFF 4,5,6 /FRL3 COATED
62992	619	INSULATION FOAM MARTIN FRL3 5M
62993	621	INSULATION FOAM NCFI 22 65
62994	621	INSULATION FOAM NCFI 22 65 CONDENSATE
62995	621	INSULATION FOAM NCFI 22 65 MACHINED
62996	621	INSULATION FOAM NCFI 22 65 NET SPRAY
62997	621	INSULATION FOAM NCFI 22 65 VANDENBERG
62998	621	INSULATION FOAM NCFI 22 65/FRL3 TY1 COATED
62999	622	INSULATION FOAM NCFI 25 13
63000	622	INSULATION FOAM NCFI 25 13 RX6
63001	622	INSULATION FOAM NCFI 362 82 POLYURETHANE
63002	622	INSULATION FOAM NCFI 367 POLYURETHANE
63003	622	INSULATION FOAM NCFI 6A POLYISOCYANURATE
63004	622	INSULATION FOAM NCFI 7A POLYISOCYANURATE
63005	782	NYLON 6 NOC
63006		DELETED SEE 63873
63007		DELETED SEE 63873
63008	1,250	POTTING COMPOUND DOLPHS CB1078/HARDNER
63009	1,253	POTTING COMPOUND PROSEAL 799
63010	1,261	POTTING COMPOUND STYCAST 2850KT/C9
63011		DELETED SEE 62319
63012	1,260	POTTING COMPOUND STYCAST 2850KT/24LV
63013		DELETED SEE 20209
63014		DELETED SEE 60352
63015	785	P-GASKET BMS 1-59 SILICONE
63016	40	ADHESIVE ARMAFLEX BLACK
63017	1,330	RUBBER SILICONE CHOTHERM 1661 WITH CHOBOND 320
63018	1,299	RUBBER LATEX FAULTLESS
63019		DELETED SEE 20762
63020	1,304	RUBBER NEOPRENE W180
63021	1,320	RUBBER SILASTIC E RTV SILICONE
63022		DELETED SEE 03484
63023	1,539	ZIPPER NOMEX COATED WITH RTV 6-1104
63024		DELETED SEE 02976
63025		DELETED SEE 63200

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006728 1 ■

MATCD	PAGE	DESIGNATION
63026	1,341	RUBBER SILICONE RA38140
63027	1,341	RUBBER SILICONE RA-5211U
63028	1,359	RUBBER SILICONE SE5206V
63029	1,362	RUBBER SILICONE SR50
63030	1,362	RUBBER SILICONE SWS7220/7250
63031	1,344	RUBBER SILICONE RTV 282 ADHESIVE
63032	1,340	RUBBER SILICONE ON AL/SILASTIC E
63033	1,369	RUBBER VITON
63034	1,374	RUBBER VITON B50
63035	1,374	RUBBER VITON B50/DZ70D610
63036	1,374	RUBBER VITON B50/DZ700610
63037	1,375	RUBBER VITON E60C
63038	1,375	RUBBER VITON E60C/HT426 NOMEX
63039	1,379	RUBBER VITON RA61375VC
63040	1,374	RUBBER VITON B50/DZ70D613
63041	630	INSULATION FOAM POLYSTYRENE/HALOCARBON 6-25 COATED
63042	630	INSULATION FOAM POLYSTYRENE/KEL-F 90 GREASE COATED
63043	1,331	RUBBER SILICONE CL 1A & 1B GR 40
63044	1,334	RUBBER SILICONE DURO 40
63046	631	INSULATION FOAM POLYURETHANE AW420
63047	611	INSULATION FOAM CPR920-9-2 POLYURETHANE PS
63048	630	INSULATION FOAM POLYURETHANE FRL3602
63049	632	INSULATION FOAM POLYURETHANE FSC55
63050	632	INSULATION FOAM POLYURETHANE FSC83A-55
63051	625	INSULATION FOAM PDL4034-2.5/ SEALED WITH DAPCOSEAL 2030
63052	624	INSULATION FOAM PDL4034-12 UNCOATED WITHOUT SUBSTRATE
63053		DELETED SEE 60451
63054	625	INSULATION FOAM PDL61
63055	625	INSULATION FOAM PDL62
63056	1,408	SPONGE RUBBER SILICONE PD200-16
63057	633	INSULATION FOAM POLYURETHANE ISOFOAM SS0991
63058	630	INSULATION FOAM POLYURETHANE LAC28-4102
63059	622	INSULATION FOAM NCFI F11-A POLYURETHANE
63061	1,408	SPONGE RUBBER SILICONE PD200-16/RTV560/PD147
63062	625	INSULATION FOAM PELLETS FRL COATED
63063	628	INSULATION FOAM POLYIMIDE OPEN CELL 17021
63064	628	INSULATION FOAM POLYISOCYANURATE FSC17A
63065	628	INSULATION FOAM POLYISOCYANURATE FSC18A
63066		DELETED SEE 63002
63067	633	INSULATION FOAM POLYURETHANE PDLX10-241
63068	623	INSULATION FOAM PBO21-44 POLYURETHANE
63069		DELETED SEE 63057
63070	629	INSULATION FOAM POLYISOCYANURATE FSC55
63071	633	INSULATION FOAM POLYURETHANE PHR50
63072	633	INSULATION FOAM POLYURETHANE P2020
63073	628	INSULATION FOAM POLYISOCYANURATE 2382-P2B
63074	629	INSULATION FOAM POLYSTYRENE
63075	630	INSULATION FOAM POLYSTYRENE/FLUORCHEM FC78
63076	629	INSULATION FOAM POLYSTYRENE/FLOUROLUBE S30 COATED
63077	630	INSULATION FOAM POLYSTYRENE/FR LATEX COATED
63078	630	INSULATION FOAM POLYSTYRENE/HALOCARB OIL 1121
63079	636	INSULATION FOAM PYRELL INSIDE BOX
63080	634	INSULATION FOAM POLYURETHANE WITH COATING URETHANE
63081	631	INSULATION FOAM POLYURETHANE FOA-1
63082	632	INSULATION FOAM POLYURETHANE HYFONIC 1
63083	633	INSULATION FOAM POLYURETHANE ISOFOAM SS0658
63084	635	INSULATION FOAM POLYURETHANE/PLV 2000/SILICONE
63085	635	INSULATION FOAM POLYURETHANE/PLV 2000/WHT PAINT
63086	634	INSULATION FOAM POLYURETHANE SFP-237
63087	634	INSULATION FOAM POLYURETHANE TEXAS 407-22
63088	634	INSULATION FOAM POLYURETHANE UTAH 100-2-30F
63089	634	INSULATION FOAM POLYURETHANE UTAH 320-315
63090	638	INSULATION FOAM PYRELL/PLV2000 HS COATED
63091	638	INSULATION FOAM PYRELL/REFSET RL4389 COATED
63093	639	INSULATION FOAM PYRELL/RTV 560 COATING
63094	639	INSULATION FOAM PYROTHANE GRADE 40/25
63095	639	INSULATION FOAM PYROTHANE GRADE 45/35
63096	639	INSULATION FOAM PYROTHANE GRADE 45/45
63097	640	INSULATION FOAM QUELFLAM SS624
63098	641	INSULATION FOAM SCOTTFELT GRADE 700ZH
63099	1,408	SPONGE RUBBER SILICONE PD200
63101	642	INSULATION FOAM SLA561/FRL COATED/DMSO GEL
63105	643	INSULATION FOAM STICK IU57/ALBICOTE FRL
63106	647	INSULATION FOAM TX39 URETHANE
63107	644	INSULATION FOAM STICK IU57/REFSET COATED
63108	644	INSULATION FOAM STICK IU57/HYPALON COATED
63109	646	INSULATION FOAM THERMOTROL 2122 POLYURETHANE
63110	646	INSULATION FOAM TU2008-45-5
63111	646	INSULATION FOAM TU2008-61-1
63112	646	INSULATION FOAM TU28 URETHANE
63113	646	INSULATION FOAM TU32 URETHANE
63114	502	FABRIC VINYL/NYLON LAMIN NOC
63115	647	INSULATION FOAM TX43 URETHANE
63116	650	INSULATION FOAM VONAR CLOTH BACKED TY 3
63117	573	HOSE FLEX ASSEMBLY/FIRE SLEEVING
63118	576	HOSE NEOPRENE CWC
63120	576	HOSE NEOPRENE TYPE A
63121	578	HOSE RTV SILICONE
63122	609	INSULATION FOAM CPR402 POUR
63124	581	ID PLATE PHOTO/MACBOND 1B1160
63125	584	INK CAT-L-INK 50-100R/20
63126	585	INK CAT-L-INK 50-700/1
63127	585	INK CAT-L-INK 50-700R/20
63128	601	INSULATION BLANKET MIN-K FAB/STEEL
63129		DELETED SEE 63421
63130	601	INSULATION CELLULOSE WITH FIREPROOFING
63131	602	INSULATION CORK AB600
63132	602	INSULATION FIBERGLASS BUILDING PINK
63133	603	INSULATION FOAM ARMAFLEX
63134	599	INSULATION AL FOIL ON BETA CLOTH
63135	655	INSULATION POLYIMIDE/GLASS RI409/SLS21
63136		DELETED SEE 63785
63137		DELETED SEE 60301
63138		DELETED SEE 06062
63139	1,485	TUBING FIBERGLASS "S"
63140	657	INSULATION STYROFOAM WHITE
63141	657	INSULATION STYROFOAM TG
63142	657	INSULATION STYROFOAM/FRL COATED

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006729 3 ■

MATCD	PAGE	DESIGNATION
63143		DELETED SEE 05332
63144		DELETED SEE 63415
63145	1,535	WIRE MAGNET NYLON/POLYURETHANE
63146	775	MTA-2
63147	782	NYLAFIL G-12/40
63148	782	NYLATRON MOS2 FILLED NYLON
63149		DELETED SEE 06286
63150	785	PAD SILICONE
63151	786	PAPER ARTIST 240-5/FASSON 824
63152	789	PAPER NOMEX/HONEYCOMB
63153	790	PAPER PERVEL LH8613
63154	687	LAMIN DC6-1104 AND REFSET COATED
63155	696	LAMIN EPOXY/GLASS FIBER
63157	691	LAMIN EPOXY/GLASS 185206
63158	713	LAMIN ON STEEL SUB WITH P223
63159	701	LAMIN EPOXY/GLASS/URALANE 5750 COATED
63160	702	LAMIN EPOXY/GLASS/URALANE 5753 COATED
63161	691	LAMIN EPOXY/GLASS
63162	763	MOLD COMPOUND DAP GREEN
63163	1,386	SEALANT AIR-O-SEAL
63165		DELETED SEE 60056
63166		DELETED SEE 05275
63167	672	LACING TAPE A050
63168	674	LACING TAPE GUDETEMP 718Z NOMEX
63169	680	LACING TAPE NYLON
63170	682	LACING TAPE POLYESTER/DACRON
63171		DELETED SEE 05925
63172	692	LAMIN EPOXY/GLASS AUGAT 8136URGI
63173	701	LAMIN EPOXY/GLASS/COPPER G10
63174	701	LAMIN EPOXY/GLASS/RL4389 COATED
63175	707	LAMIN EPOXY/PLASTIC
63176	698	LAMIN EPOXY/GLASS ON AUGAT UL1
63177	708	LAMIN FIBERITE MXB5004/1581
63178		DELETED SEE 06382
63179	701	LAMIN EPOXY/GLASS/SCOTCHCAST 251
63180	719	LAMIN VITON B50/KEVLAR 49/181
63181	722	LENS MAKROLON 3900LS
63182		DELETED SEE 05197
63183	729	LUBE DRY GP1904
63184	761	MICROSWITCH WITH KEYS
63185	778	MULTI-LAYERED INSULATION GOLDIZED KAPTON
63186	780	MULTI-LAYERED INSULATION TEDLAR/NOMEX/KAPTON
63187	775	MULTI-LAYERED INSULATION 3M838 TEDLAR/NOMEX/KAPTON
63188	775	MSA-1/TURCO T6109 TOPCOAT
63189	775	MSA/HYPALON HFR2200/ACTIVATOR
63190	775	MSA FOAM COATED WITH HYPALON HFR2200
63191	1,396	SEALANT URETHANE S183026
63192	281	B150L FIBERGLASS REINFORCED
63193	424	DAP VINYL/GRAPHITE
63194		DELETED SEE 60264
63195	1,243	POREFLON P/N FP080 PTFE
63196	1,361	RUBBER SILICONE SILIGAN J500
63197	1,469	TEFLON DEGREASED VACUUM BAKED
63198		DELETED SEE 60301
63200	1,333	RUBBER SILICONE DC Q3-6567 A/B
63201		DELETED SEE 20017
63202	1,493	TUBING POLYCHLOROPRENE HST
63203		DELETED SEE 05340
63204	1,496	TUBING POLYOLEFIN RT360 TYPE 2
63205		DELETED SEE 00367
63206	1,402	SOCKET NYLON/GLASS FILL
63207	1,403	SOUNDSCREEN FOAM/METAL/FOAM
63208	1,364	RUBBER SPONGE VITON
63209	1,411	STREAMER WARNING COTTON
63213		DELETED SEE 06188
63214	1,426	TAPE KEVLAR POLYURETHANE COATED
63218	1,424	TAPE HI-TEMP ACRYLIC ADHESIVE
63219		DELETED SEE 06531
63220		DELETED SEE 61260
63221	1,413	TAPE ALUMINIZED KAPTON 14162-51
63222	1,417	TAPE ELECTRIC POLYESTER TYPE GFT PS ADHESIVE
63223	1,418	TAPE FLUORGLAS 2915 PS ADHESIVE
63224		DELETED SEE 61409
63225		DELETED SEE 02897
63226	406	CONNECTOR DAP 280-35001-208
63227	1,434	TAPE NOMEX RF466/COATING VITON B50
63228	1,434	TAPE NYLON WEBBING WHITE
63229	635	INSULATION FOAM POLYURETHANE/TAPE AL 7402
63230	1,434	TAPE OKONITE 35 JACKETING
63231	1,435	TAPE P11 ALUMINUM FOIL
63232		DELETED SEE 61139
63233	1,459	TAPE SCOTCHMOUNT 4032
63234	1,460	TAPE SILICONE MOX/FIBERGLASS
63235	1,437	TAPE P421 TEFLON SILICONE ADHESIVE
63236	1,449	TAPE SCOTCH 56 POLYESTER
63237		DELETED SEE 61407
63238	1,465	TAPE TEMP-R-TAPE ON TEDLAR FILM
63239		DELETED SEE 61787
63240	1,412	TAPE 6083 TFE/GLASS
63241	1,466	TAPE VIDEO RCA 3M361
63242	1,467	TAPE VIDEO RCA 3M400
63243	1,437	TAPE P29 VINYL BLACK ELECTRIC
63244		DELETED SEE 63287
63245	1,516	WEBBING KEVLAR 1813-2
63246	1,535	WIRE JUMPER NYLESE/PC18M COATED
63247	1,537	YARN POLYESTER 1100 DENIER
63248	1,539	ZIPPER NOMEX/COATING VITON B50
63249		DELETED SEE 63248
63250	1,539	ZIPPER NOMEX VF106
63251	514	FASTENER VELCRO NOMEX LOOP 2000 WITH PS 0372 ADHESIVE
63252	1,452	TAPE SCOTCH 8417 CLEAR/8418 OPAQUE
63253	1,474	THERMAL LAG FR MATERIAL
63254	1,495	TUBING POLYOLEFIN HST CLEAR
63255	1,487	TUBING FLEXAFIT SG2122
63256	1,490	TUBING JUNFLON PFA
63257		DELETED SEE 06621
63258	1,491	TUBING KYNAR HST/KYNAR BLACK/ALUMINUM
63259		DELETED SEE 00367
63260		DELETED SEE 65318

MSFC-HDBK-527 REV F 9999942 0006730 T

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
63261		DELETED SEE 05974
63262	1,491	TUBING KYNAR PVF175 HS
63263	1,497	TUBING POLYURETHANE CABLE JACKET
63264		DELETED SEE 20427
63265		DELETED SEE 63866
63266		DELETED SEE 61041
63267		DELETED SEE 60911
63268	522	FASTENER VELCRO NYLON LOOP 200 PS 3072
63269	510	FASTENER VELCRO HOOK 80 PS 3072
63270	519	FASTENER VELCRO NYLON HOOK ADHESIVE BACK
63271		DELETED SEE 61037
63272	514	FASTENER VELCRO NYLON 100 BACKING 0172AB
63273		DELETED SEE 61040
63274		DELETED SEE 60299
63275	509	FASTENER VELCRO HAQ 12-2 HOOK AND LOOP BACKING RUBBER SILICONE
63276	508	FASTENER VELCRO ARAMID HOOK 65 AND LOOP
63277	509	FASTENER VELCRO HI-AIR NOMEX HOOK 65 AND LOOP 2000
63278	519	FASTENER VELCRO NYLON HOOK AND LOOP 65 BACKING 0399
63279		DELETED SEE 05205
63280	694	LAMIN EPOXY/GLASS CIRCUIT BOARD
63281		DELETED SEE 62744
63282		DELETED SEE 62745
63283		DELETED SEE 62776
63284	464	FABRIC KEVLAR GAC-RF443
63285		DELETED SEE 62790
63286		DELETED SEE 62789
63287	1,452	TAPE SCOTCH 838 TEDLAR
63289		DELETED SEE 63118
63290		DELETED SEE 63530
63291	755	LUBE OIL SRG 10
63292	751	LUBE OIL APIEZON C
63293	1,243	POLYPHENYL ETHER 4 AND 5 RING
63294	83	ADHESIVE CYANOACRYLATE
63295	69	ADHESIVE CHEMGRIP
63296	289	CABLE COAX CU/AU 250-3866-0000
63297	659	INSULATION WIRE CU/TFE/GL
63299		DELETED SEE 05732
63300	414	CONNECTOR SEALING PLUG AL/NI
63301	1,257	POTTING COMPOUND STYCAST 1090 FR
63303	388	COATING SOLITHANE 113/300/CABOSIL
63305		DELETED SEE 20877
63306	1,530	WIRE ELEC RAYCHEM 44 BETAWRAP
63307		DELETED SEE 20877
63308		DELETED SEE 62495
63309		DELETED SEE 05332
63310	1,533	WIRE ELEC THERMOCOUPLE FIBERGLASS
63311	1,529	WIRE ELEC POLYIMIDE/KYNAR RT850
63315	1,263	POWDER GRAPHITE P692
63316		DELETED SEE 05275
63317		DELETED SEE 63167
63318	427	DREWGARD 100
63319	427	DREWGARD 187
63320	1,466	TAPE THREAD SEAL PTFE AQM
63321	382	COATING REFSET
63322		DELETED SEE 60301
63323	1,393	SEALANT SILICONE CARBIDE
63324	400	COMPOUND LEAK TEST
63325	1,294	RUBBER KALREZ 1045R
63326	1,295	RUBBER KALREZ 1046R
63327	1,295	RUBBER KALREZ 1046RM
63328		DELETED SEE 62820
63329		DELETED SEE 62820
63330		DELETED SEE 00016
63331	1,262	POWDER ALKALUME 1744
63332	752	LUBE OIL FLUOROLUBE LG160
63334		DELETED SEE 62820
63335	1,485	TUBING FIBERGLASS
63336	560	FLUOROLOY K
63380		DELETED SEE 62591
63381		DELETED SEE 05332
63382	1,523	WIRE ELEC BMS 13-46 26 AWG
63383		DELETED SEE 06103
63384		DELETED SEE 05449
63385		DELETED SEE 05205
63387	437	FABRIC BETA CLOTH/TFE GLASS TAPE
63388	429	ELECTRICAL ASSEMBLY
63389	561	FOAM PYRELL FOAM/IN METAL TOOLBOX
63390	630	INSULATION FOAM POLYSTYRENE/HI VISC BFC FLUID
63391	634	INSULATION FOAM POLYURETHANE PQ2
63392	633	INSULATION FOAM POLYURETHANE P4
63393	632	INSULATION FOAM POLYURETHANE FSC8BA55 P-2
63394	600	INSULATION BLANKET AU/AL COATED
63395	600	INSULATION BLANKET AU/AU COATED POLYIMIDE
63396	655	INSULATION RAPCO
63397	700	LAMIN EPOXY/GLASS VIBRATION DAMPER
63398	700	LAMIN EPOXY/GLASS WITH HRH
63399	760	MASKS DIVING NAVY RUBBER/PLAS
63400		DELETED SEE 63280
63401		DELETED SEE 63280
63403	344	COATING ECCOCOAT EC 210
63404	1,268	RING PLASTIC ON METAL DIODE
63405	1,376	RUBBER VITON MDAC 18210-16
63406	1,404	SPONGE MOSITE
63407		DELETED SEE 62859
63408		DELETED SEE 63409
63409	292	CABLE ELEC TFE/VARGLAS SLEEVE
63410	292	CABLE ELEC TFE/BEN-HAR SLEEVE
63411	292	CABLE ELEC TFE/BEN-HAR GLUE
63412		DELETED SEE 62740
63413	292	CABLE ELEC NILCO/TFE/NYLON/NOMEX/AL
63414		DELETED SEE 05451
63415	1,532	WIRE ELEC REINSHAGEN POLYIMIDE
63416	571	HARNESS TENSOLITE ASSEMBLY 20AWC
63417	293	CABLE ELEC TFE/VARGLAS SLEEVE
63418	292	CABLE ELEC PTFE WITH SHEATH TAPE
63419		DELETED SEE 62807
63420		DELETED SEE 63409
63421	1,533	WIRE ELEC TFE/GLASS WARP

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006731 1

MATCD	PAGE	DESIGNATION
63422	294	CABLE HARNESS ASSEMBLY QUIRK 22AWG
63423		DELETED SEE 63421
63424		DELETED SEE 63421
63425		DELETED SEE 63421
63426		DELETED SEE 63411
63427		DELETED SEE 63421
63428	391	COATING TURCO T6109/ELECTRODAY 500
63429	396	COMPOSITE DACRON/MYLAR/NYLON
63430	1,493	TUBING NOMEX/TEFLON/SILICONE
63431	762	MOLD COMPOUND BMC-15 6100 POLYES/GL
63432	397	COMPOSITE SRB THERMAL CURTAIN
63433	397	COMPOSITE GLASS/AL/934 RESIN
63434	294	CABLE HARNESS ASSEMBLY/TFE/BEN-HAR
63436	285	BELLOWS/TUBE FLEXAFIT SG2212
63438	303	CHEMPOL/BETA CLOTH/113-300
63439	775	MULTI-LAYERED INSULATION AL/AU COATED/VELCRO/ ACRYLIC
63440	779	MULTI-LAYERED INSULATION PLASTIC/VELCRO/AU COATED
63441	776	MULTI-LAYERED INSULATION ALUMINIZED KAPTON GDC
63442	776	MULTI-LAYERED INSULATION ALUMINIZED KAPTON/Y966
63443	778	MULTI-LAYERED INSULATION DACRON/MYLAR/ARMALON/TFE
63453		DELETED SEE 62235
63454	41	ADHESIVE ARMSTRONG A2/E
63455		DELETED SEE 06365
63456	281	BAG CAMERA
63457	283	BATTERY CELL ZN-AIR 630HP
63458	287	BOTTLE VACUUM SERIES #2
63459	287	BOTTLE VACUUM #SL-4VBA
63460		DELETED SEE 05417
63464		DELETED SEE 63451
63468	282	BAG NYLON/POLYETHYLENE/RUBBER
63469	283	BARRIER FIBERTRAX HOTBOARD
63470	287	BOX APEX TAPE
63471		DELETED SEE 05784
63472		DELETED SEE 05646
63473	358	COATING KODAK REFLECTIVE WHITE
63475	437	FABRIC BETA CLOTH/PLASTIC COATED
63476	439	FABRIC BUNTING PANTS 31801
63477	444	FABRIC COTTON TWILL
63478	472	FABRIC NOMEX BLUE FLIGHT SUIT
63479	489	FABRIC PELLON #7015
63480	493	FABRIC QUARTZ
63481	555	FILTER CARTRIDGE PTFE
63482	595	INK SILKSCREEN RED
63483	596	INK TEC BLACK #1501
63484	656	INSULATION SOUND KNB5LR PVC/GL/PB
63485		DELETED SEE 20877
63486	696	LAMIN EPOXY/GLASS FB600
63488		DELETED SEE 62236
63489	306	CLEANER BRAYCOTE 137
63490		DELETED SEE 05924
63491		DELETED SEE 00016
63492	748	LUBE GREASE SLICK 50
63493	756	LUBE ROYCO 13D
63494	1,334	RUBBER SILICONE DURO 70
63495	779	MULTI-LAYERED INSULATION KAPTON/DACRON/BETA COVERED
63496	776	MULTI-LAYERED INSULATION AL/MYLAR/KEVLAR/DACRON
63497	778	MULTI-LAYERED INSULATION FEP/GLASS/POLYIMIDE/ KEVLAR
63498	795	PEN UNIMARK 960
63499	995	PLASTIC MINI-TOGGLE ABS
63500	1,282	RUBBER EPDM NOC
63501	1,349	RUBBER SILICONE RTV 560/9811
63502	1,337	RUBBER SILICONE HT 2-80 SHOCK ISOLATOR
63503		DELETED SEE 05122
63504	1,368	RUBBER URINE COLLECTION TUBE
63505	296	CALSPAN SEAL SETS 67/151007
63506	3	ACRYLIC TYPE 350S
63507	1,398	SHIM AL 50524H39
63508	1,402	SOCKS PATAGONIA
63509	1,413	TAPE ALL WEATHER CW3
63510	1,430	TAPE MYLAR/SILVER ADHESIVE
63511	357	COATING INK/ADHESIVE ON LEXAN
63512	572	HOKE MULTIMITE 5-WAY BALL VALVE
63513	440	FABRIC COTTON BLUE MOUNTAIN
63515	495	FABRIC SHIRT
63518	704	LAMIN EPOXY/GRAPHITE HE1034E
63519	885	PLASTIC ELECTROSAFE
63520	598	INK WORNOWINK M-6-N/CAT A
63521	775	MULTI-LAYERED INSULATION AL/FEP/DACRON/POLYMIDE
63522	535	FILM EKTRACHROME 5020
63523		DELETED SEE 06230
63524	600	INSULATION BLANKET DP50392 TYPE 2 MYLAR/KAPTON
63525		DELETED SEE 63952
63526	187	ADHESIVE LOCTITE BLACK MAX
63527	1,494	TUBING POLYETHYLENE HST
63528	455	FABRIC GLASS/NOMEX S2283R
63529	648	INSULATION FOAM URETHANE CMHR
63530	410	CONNECTOR ELECTRICAL
63556	509	FASTENER VELCRO ASTRO HOOK AND LOOP
63573		DELETED SEE 63555
63574		DELETED SEE 63551
63577		DELETED SEE 63569
63640	541	FILM MAGAZINE
63642	535	FILM EKTACHROME VIDEO NEWS
63650	305	CLAMP SILICONE/FABRIC TA 321
63662	282	BAG POLYETHYLENE RCAS 1200
63663	666	LABEL IDENTIFICATION
63664		DELETED SEE 62766
63666		DELETED SEE 62779
63668	597	INK UNIGLAZE UGLZ8000 BLACK
63669		DELETED SEE 60643
63674	541	FILM MAGAZINE 16MM
63695	657	INSULATION TERMINAL 570-1994-XX0100
63697		DELETED SEE 05275
63698		DELETED SEE 05732
63699		DELETED SEE 62517
63703	744	LUBE GREASE HYLOMAR PL32
63709		DELETED SEE 60611

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006732 3

MATCD	PAGE	DESIGNATION
63710		DELETED SEE 62408
63711		DELETED SEE 62409
63714	297	CAP DISPENSER TOOTHPASTE
63715	1,416	TAPE DOUBLE STICKY BACK DVF1
63716	1,392	SEALANT POLYURETHANE PR1660
63717	302	CHAMBER MODULE CROSS SECTION
63718	637	INSULATION FOAM PYRELL/DC3140/UBS-N136
63723	458	FABRIC GORTEX TRICOT/PTFE
63724	49	ADHESIVE BACON FA8-BA5 COATED WITH SCOTCHCAST 280 B/A
63726	533	FILM CAPRAN 518 GREEN
63727	546	FILM NYLON RCAS 2400 ORANGE
63728	103	ADHESIVE EA9326 EPOXY
63734	776	MULTI-LAYERED INSULATION BLANKET THERMAL
63735	434	FABRIC 65 POLYESTER/35 COTTON
63736	449	FABRIC DURETTE 420-2
63737	449	FABRIC DURETTE 430-13
63739	631	INSULATION FOAM POLYURETHANE FR
63741	1,417	TAPE FASTAPE A PS
63743	1,410	STORAGE CAN FOR RECORDING TAPE
63746	1,271	RUBBER ALLOY L065-72A
63750	1,512	VESTIBULAR EXPERIMENT MIDDECK TRAY
63752	1,512	VESTIBULAR EXPERIMENT DOME STOWAGE
63753	1,512	VESTIBULAR EXPERIMENT MICROCOMPUTER
63754	1,512	VESTIBULAR EXPERIMENT BRS
63755	486	FABRIC P310 ULTRA
63756	487	FABRIC P313
63758	283	BATTERY DURACELL 9 VOLT MN1604
63760	294	CABLE HARNESS 3AFT 23-15
63761	331	COATING CHEMGLAZE A471 POLYURETHANE GRAY
63762	369	COATING POLANE TOPCOAT/KEVLAR
63763	502	FABRIC TYVEK 1442
63764	1,388	SEALANT GRAPHITAR 114/CARBON
63765	317	COATING 821-425/515-700 PRIMER
63766	794	PEN LUMOCOLOR 313 SF
63767	303	CLAMP CABLE ADEL 1408
63768		DELETED SEE 05205
63769	1,424	TAPE KAPTON AND TAPE HOLDER
63770	762	MOLD COMPOUND AKEMI #4
63771	657	INSULATION STYROFOAM
63772		DELETED SEE 61273
63773	647	INSULATION FOAM UNICELLULAR POLYETHYLENE
63774	545	FILM NYEBAR CT FLUOROCARBON BARRIER
63775	397	COMPOSITE KEVLAR/VITON
63776	1,535	WIRE GSC 1620
63777	548	FILM PHOTOMICROGRAPHIC COLOR
63778		DELETED SEE 63256
63779	1,261	POTTING COMPOUND SUMICERAM S10A
63781	1,502	TUBING THERMOFIT HS
63782		DELETED SEE 62725
63783		DELETED SEE 62723
63785	398	COMPOSITE VITON E60C/NOMEX HT426
63786	1,242	PLATES LEAD
63787	304	CLAMP FOR LEAD PLATES
63788		DELETED SEE 63283
63789		DELETED SEE 63284
63790	738	LUBE GREASE BEACON 325
63791		DELETED SEE 63118
63792		DELETED SEE 63287
63793		DELETED SEE 63291
63794		DELETED SEE 63292
63795		DELETED SEE 63295
63796		DELETED SEE 63294
63797	288	BRAID NYLON ELASTIC
63799		DELETED SEE 62291
63855		DELETED SEE 62756
63856		DELETED SEE 63218
63857		DELETED SEE 62716
63858	282	BAG ZIP LOCK VINYL ACETATE
63859		DELETED SEE 61409
63860	793	PEN BEROL POROUS TIP/INK 7722
63861	484	FABRIC NYLON-OXFORD
63862		DELETED SEE 62787
63863	405	CONNECTOR CONTACT 7219
63865	550	FILM RCA
63866	1,502	TUBING TEFLON TFE ZEUS 14 HST
63867	787	PAPER E-20
63868	787	PAPER E-20 WITH PPC TONER SF-88T
63869	562	GASKET MONEL/SILICONE DURO SOLID
63870		DELETED SEE 63221
63871	445	FABRIC COTTON/LYCRA
63872	720	LAMINATED SHIM STOCK
63873	948	PLASTIC IUPILON POLYCARBONATE
63874	390	COATING TOPCOAT YELLOW
63875		DELETED SEE 63195
63876	671	LABELS PAPER P/S
63877	786	PAPER BOND HIGH RAG CONTENT
63878		DELETED SEE 05296
63879		DELETED SEE 63151
63880	282	BAG RECLOSABLE POLYURETHENE
63881	1,399	SIEVE MOLECULAR
63882		DELETED SEE 62742
63883		DELETED SEE 62741
63884		DELETED SEE 63027
63885	423	COVER DUST FES BETA/VELCRO
63887	556	FILTER MATERIAL HEPA
63888	566	GLOVE INSULATED FES 3MF114AP
63889		DELETED SEE 62717
63890	1,482	TOWELETTES WASH 'N DRI
63891		DELETED SEE 63234
63892	785	PAD PREP PROVIDINE-IODINE
63893	784	OINTMENT POLYSPORIN ANTIBIOTIC
63894		DELETED SEE 63183
63896	406	CONNECTOR ELEC 13% GLASS/NYL
63898	698	LAMIN EPOXY/GLASS PC BOARD
63900		DELETED SEE 62745
63901		DELETED SEE 62790
63902		DELETED SEE 62789
63903		DELETED SEE 63288
63906	289	CABLE COAX

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006733 5 ■

MATCD	PAGE	DESIGNATION
63908		DELETED SEE 63300
63915	505	FASTENER POLYESTER SLIDE 321
63918		DELETED SEE 62856
63919	1,394	SEALANT SPIRASEAL METAL/TFE
63920	1,243	POLYSTYRENE PETRI DISH
63921	504	FASTENER DENISON
63922		DELETED SEE 62201
63923	501	FABRIC TEFLON/COATED BETA CLOTH
63924	1,271	RUBBER BUMBER
63926	473	FABRIC NOMEX FELT X-547
63930		DELETED SEE 06106
63937		DELETED SEE 05182
63939	760	MELAMINE WASHERS
63940	1,458	TAPE SCOTCHCAL 639
63941		DELETED SEE 05582
63942		DELETED SEE 06382
63943	728	LUBE DRY EVERLUBE 620C
63944		DELETED SEE 00543
63945	261	ADHESIVE THREE SEALING COMPOUND
63947	760	MASK SOLDER PC501-GREEN
63948	1,425	TAPE KAPTON/DACRON/CHEMGLAZE
63949	1,192	PLASTIC ULTEM 1000
63951		DELETED SEE 62779
63953		DELETED SEE 05405
63954	571	HEATER AUTOTRACE 10PTV1 18 AWG
63955	1,530	WIRE ELEC RAYCHEM 44 FABRIC/MESH
63956		DELETED SEE 63306
63957		DELETED SEE 63306
63958	1,532	WIRE ELEC RAYCHEM CU/MYLAR/KAPTON
63959		DELETED SEE 60710
63960	1,527	WIRE ELEC KAPTON TAPE/GLASS TUBE
63961	292	CABLE ELEC COONER AS155-28-2SJ
63962	1,528	WIRE ELEC PD-219-21
63963	424	DELECTED SEE 20877
63964		DELETED SEE 20756
63965	1,530	WIRE ELEC PVC INSULATED POLYAMIDE JACKET
63966	1,529	WIRE ELEC POLYETHYLENE
63967	1,385	SEALANT 25% GLASS FILLED TFE
63968	1,385	SEALANT 15% GLASS FILLED TFE
63969	1,268	RING 60% BRONZE FILLED TFE
63970		DELETED SEE 61095
63972	1,242	PLATING GOLD ON A-286
63973	318	COATING 823-363 POLYURETHANE GLOSS ORANGE
63974		DELETED SEE 20250
63975	1,403	SOUND INSUL KNM-50B
63979	544	FILM MYLAR TYPE A
63980	502	FABRIC UNITIKA 1
63987	17	ADHESIVE ABLEBOND 414-1
63990	282	BANDAGE ELASTIC ADHESIVE 1"WIDE
63991	414	CONNECTOR THERMAL PLASTIC
63992	722	LIGHT-WELD 182 ACRYLIC ADHES
63993	1,412	TAPE AL/KAPTON/DACRON/CHEMGLAZE 202
63994	722	LIGHT-WELD 181/ACRYLIC ADHES
63995	596	INK TMS ON KYNAR/VITON SHEETS
63997	1,440	TAPE POLYETHYLENE CW3

MATCD	PAGE	DESIGNATION
64002	547	FILM PHOTO PAN 2415
64005	1,281	RUBBER DYAD 606
64009	785	PACKAGING MATERIAL RUBBERIZED HAIR
64011	546	FILM PHOTO EKTACHROME QX851
64013		DELETED SEE 60369
64014	585	INK CAT-L-INK 50-70 EPOXY
64015	555	FILM VERLCULOR VPS488 TYPE S
64020		DELETED SEE 06603
64023	1,299	RUBBER LATEX GLOVES
64024	750	LUBE GREASE X5-8003 SILICONE
64025	761	MICROHEMATOCRIT TUBE HOLDER
64026	324	COATING ALKYD-MELAMINE ENAMEL
64028	289	BRUSH AL/WOOD/CAMEL HAIR
64031	502	FABRIC VIP INTERLOCK KNIT
64032	486	FABRIC P101VIP
64034		DELETED SEE 06633
64035	435	FABRIC AIRC-S236
64036		DELETED SEE 60738
64037	1,454	TAPE SCOTCH X1181
64038	536	FILM G412500 POLYIMIDE/ARAMID
64039	537	FILM G414000 POLYIMIDE/GLASS
64040	536	FILM G413200 FEP/POLYIMIDE
64041	693	LAMIN EPOXY/GLASS CE9010A/120
64042	1,423	TAPE G412400 FEP/POLYIMIDE/ARAMID
64043	1,419	TAPE G400200 2.0 MIL TYPE A TEFLON WITH VAC DEPOSITED ALUMINUM WITH 966 ACRYLIC ADHESIVE
64044	1,419	TAPE G103760 FEP/ARAMID
64045	1,475	THREAD ARAMID
64046		DELETED SEE 06605
64047		DELETED SEE 06456
64051	602	INSULATION ENAMEL #300 RED
64052	343	COATING DURAFILM ENAMEL
64055	351	COATING EVA PATCHES
64058	478	FABRIC NOMEX-KEVLAR/TFE/GORTEX
64059		DELETED SEE 62503
64060	747	LUBE GREASE SILICONE
64061		DELETED SEE 00030
64062		DELETED SEE 05726
64063		DELETED SEE 60738
64064	1,302	RUBBER NEOPRENE CR70
64065	251	ADHESIVE SOLUBOND 1121
64068		DELETED SEE 63126
64069	1,463	TAPE TEFLON/SILICONE
64070	445	FABRIC CWV2/SOLUBOND 1128
64071	411	CONNECTOR INSERT SILICONE/RUBBER
64072	961	PLASTIC LEXAN SG403-82311
64075	715	LAMIN POLYETHYLENE/PLASTIC
64078	774	MOLDING COMPOUND HYLOMAR PL32L-25
64079	372	COATING POLYURETHANE CONFORMAL U2863
64080	323	COATING ACRYLIC CLEAR 90-10530
64081	316	COATING 68U-1005/U3380 POLYURETHANE
64087	568	GRAPHITE GR-GTA/GRAFOIL
64088		DELETED SEE 20209
64090	298	CARTRIDGE DATA DC 300A
64091		DELETED SEE 06188

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006734 7

MATCD	PAGE	DESIGNATION
64092	535	FILM EKTACHROME EE2241 (4001)
64096	716	LAMIN POLYIMIDE/GLASS
64097	664	KIT FLIGHT EXPERIMENT CARRY-ON
64098	1,363	RUBBER SILICONE TH1006
64099	1,412	TAPE ADHESIVE SILICONE GLASS/REINFORCED
64100		DELETED SEE 63183
64101	556	FILTER MATERIAL VERSAPOR 10000
64102	669	LABEL METALPHOTO
64103	537	FILM HS6262 VAC PAK NYLON
64104	627	INSULATION FOAM POLYETHYLENE/EC2241 COAT
64105	1,347	RUBBER SILICONE RTV 501-7
64106	365	COATING NEXTEL 900 WHITE
64107	84	ADHESIVE DAC2 SILICONE
64108	786	PANELS AL PAINTED W136231
64109	1,482	TOYS ASSORTED
64110	1,402	SOLUTION 12% STERICIDE
64111		DELETED SEE 00903
64112	540	FILM KODAR 6763
64113	786	PAPER COATED
64114	1,348	RUBBER SILICONE RTV 560 EPOXY/GLASS
64115		DELETED SEE 62528
64116	342	COATING DIMETCOTE #6
64118	758	MARKER STRIP NEMA GR XPC
64120	410	CONNECTOR ELECTRICAL
64122	504	FASTENER HL410V
64123		DELETED SEE 63447
64124	569	GUIDE LINER 2.5 STEM
64125	569	GUIDE LINER 1.5 STEM
64126	562	GASKET MATERIAL/GOLD
64128	1,397	SEALS PTFE KC103-4
64129	1,397	SEALS PTFE KC103-6
64130	1,397	SEALS PTFE KC103-8
64131	1,397	SEALS PTFE KC103-10
64132	1,397	SEALS PTFE KC103-12
64133	1,397	SEALS PTFE KC103-20
64134	1,397	SEALS PTFE KC103-16
64135	1,397	SEALS PTFE KC103-24
64136		DELETED SEE 63757
64138	325	COATING AR7 ON CRES 304
64140	1,415	TAPE DISSOLVO WELDING ADHESIVE
64141	1,457	TAPE SCOTCHCAL 3930
64145	511	FASTENER VELCRO KNIT NYLON LOOP 3005 BACKING 0699
64146		DELETED SEE 20209
64147		DELETED SEE 60911
64148	512	FASTENER VELCRO NOMEX HI-AIR LOOP 2000 PS 0372
64149	508	FASTENER VELCRO ASTRO HOOK 80 BACKING PS 3072
64150	509	FASTENER VELCRO ASTRO LOOP 200 PS 3072
64151	513	FASTENER VELCRO NOMEX LOOP 1000 BACKING 039
64152		DELETED SEE 60863
64153	511	FASTENER VELCRO LOOP 2000 BACKING 0100AB
64154	518	FASTENER VELCRO NYLON HOOK 80
64155	517	FASTENER VELCRO NYLON HOOK 65 LOOP 1000 BACKING 2699
64156	516	FASTENER VELCRO NYLON HOOK 65 BACKING PS 0100
64158	780	MULTI-LAYERED INSULATION TEDLAR/MYLAR/VELCRO #65
64161	1,374	RUBBER VITON CHECK VALVE
64169		DELETED SEE 05084
64176	1,440	TAPE POLYIMIDE PS
64178	1,330	RUBBER SILICONE CHOTHERM 1671
64180	596	INK TEC BLACK
64181	542	FILM MYLAR "S"
64182	784	OAK BOARD UNCOATED
64183	339	COATING DC 1-2577/C 176
64184	1,524	WIRE ELEC CU/VARGLAS/TFE
64186	688	LAMIN DUROID BOARD 6006
64187	1,251	POTTING COMPOUND EE4215/HD3615
64194	688	LAMIN DUROID BOARD 6010
64195	83	ADHESIVE DAC1
64196	426	DIAPHRAGM SILICONE/NOMEX
64198	784	OAK BOARD COATED WITH KPR
64199	568	GRAPHITE FIBERITE HMF EPOXY
64200	577	HOSE R502-16Z TEFLON
64202	577	HOSE R502-6 TEFLON
64203	384	COATING SCOTCHGARD FC326
64205	1,251	POTTING COMPOUND EPON 828/ALUMINUM/TONOX
64206	549	FILM POLYIMIDE/ALUMINUM/NOMEX/SCRIM
64207	293	CABLE ELEC URETHANE J210/BLK
64208	539	FILM KAPTON/GLASS/BETA 107 BLK
64210	1,314	RUBBER POLYURETHANE SORBOTHANE/50
64211	1,314	RUBBER POLYURETHANE SORBOTHANE
64214	405	CONNECTOR D-SUB DEM/DAM/DBM
64217	424	DEBRIS FROM ISS-DEBRIS TRAP
64218		DELETED SEE 63764
64219	17	ADHESIVE ABLEBOND 36-2 EPOXY
64220	295	CABLE TIES NOMEX/POLYETHYLENE FC4101
64230	352	COATING FILAMENT WOUND KELVAR
64231	557	FLUIDTRONICS LIP SEAL
64233		DELETED SEE 80099
64235	404	CONN MPE PROTECTIVE CAPS
64236	404	CONN TERMINAL FUNCTION MODULES
64238	1,294	RUBBER HOSE LOW PRESSURE
64239	1,299	RUBBER MAT
64240	165	ADHESIVE FILM FM123-5
64244	593	INK POLY PRINT 45NL75/45NL99
64245	1,402	SOLDER SLEEVE D101-00
64246		DELETED SEE 20209
64247	315	COATING 6725-1 PRIMER
64257	1,418	TAPE FLUORGLAS 2346-1 ADHESIVE
64261	793	PEN BIC FS11
64262	548	FILM PHOTOSENSITIVE SCOTCHCAL
64264	1,253	POTTING COMPOUND PR1201Q
64265	678	LACING TAPE NOMEX GUDE-TEMP
64269	401	COMPOUND TA2417 SILICONE
64271	538	FILM KAPTON AL/BETA 107/GLASS
64273	538	FILM KAPAK/SCOTCHPAK
64276	786	PAPER COLORPHAST PH #9582
64278	337	COATING CONDUCTIVE INK #703-5-1
64282	534	FILM COLORSLIDE 1000/135-36
64286	698	LAMIN EPOXY/GLASS S901
64287	530	FIBERGLASS/EPOXY EF2/59

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006735 9

MATCD	PAGE	DESIGNATION
64288	693	LAMIN EPOXY/GLASS CE9010A/7781
64290	1,436	TAPE P214 GLASS/ACRYLIC
64292	402	COMPOUND URALANE/GLASS 5753LV A1
64293	757	MAGNETIC CORE T12-60
64294	285	BELT (TIMING) POLYURETHANE
64295	402	COMPOUND URALANE/GLASS 12887-556
64296	402	COMPOUND URALANE/GLASS 5753LV B1
64297	402	COMPOUND URALANE/GLASS 5753LV C1
64298	402	COMPOUND URALANE/GLASS 5753LV X1
64299	402	COMPOUND URALANE/GLASS 5753LV V1
64300	403	COMPOUND URALANE/GLASS 5753LV Z1
64301	402	COMPOUND URALANE/GLASS 12887-547
64302	577	HOSE R502-8 TEFLON
64304	624	INSULATION FOAM PDL4034-2.5 WRAPPED WITH ARAMID SLEEVING/COATED WITH PR1660/SEALED WITH DAPCOSEAL 2030
64306	582	INK 42-11FD MARKING BLACK
64312	581	INK 41 BLACK PASTE
64315	747	LUBE GREASE SH340
64316	750	LUBE GREASE Y VAC 3
64317	541	FILM LUMILOR POLYESTER INSULATION
64321	426	DEODORANT SPEED STICK
64322	1,333	RUBBER SILICONE CV2500
64323	625	INSULATION FOAM PDL4034-2.5/COVERED WITH L-T-80 TAPE/SEALED WITH DAPCO 2030
64324	344	COATING E393025N BLACK EPOXY
64325	1,446	TAPE SCOTCH 438
64328	624	INSULATION FOAM PDL4034 COVERED WITH L-T-80 TAPE AND THEN G401000 TAPE
64329	631	INSULATION FOAM POLYURETHANE 50150
64330	369	COATING POLANE ENAMEL
64333	784	O-RINGS SPARE FOR FES FURNACE
64334	253	ADHESIVE STANPAT
64437	349	COATING EPOXY POLYIMIDE
64438	349	COATING EPOXY POLYIMIDE/PRIMER
64439	359	COATING LAC-O-RITE
64440	380	COATING PT111 LACQUER
64441	380	COATING PT401 RESIN
64442	387	COATING SILICONE/PRIMER
64443	496	FABRIC SILICONE/GLASS
64446	699	LAMIN EPOXY/GLASS STRIPPED
64447	710	LAMIN GLASS CLOTH
64448	781	NAMEPLATES SSME
64449	788	PAPER FIBERFRAX
64450	1,304	RUBBER NEOPRENE R/C1960
64451	1,353	RUBBER SILICONE RTV 7500-511/FIBERGLASS
64452	1,353	RUBBER SILICONE RTV 77
64453	1,362	RUBBER SILICONE T8296
64456	1,347	RUBBER SILICONE RTV 3145/DC1200
64459	1,482	TRANSITE
64460	1,482	TRANSITE PT401 COATED
64462	455	FABRIC GLASS/LAMIN 3171/PT401
64463	455	FABRIC GLASS/LAMIN 3171 RESIN
64464	494	FABRIC RTV E 1581 GLASS
64465	1,262	POTTING COMPOUND URETHANE
64466	672	LACING TAPE AROMATIC POLYAMIDE
64493	1,423	TAPE G411600 AL-KAPTON/ORGANIC COATED
64505	1,514	WEBBING DACRON 2300 LB
64800	784	ORBITAL MAP AND COVER
64801	557	FLIGHT DATA FILE JCPK20
64802	557	FLIGHT DATA FILE JCPK10
64803	404	CONFIG SEE05387/88/89/90/91/92
64804	280	ALTITUDE OXYGEN HOSE
64805	475	FABRIC NOMEX K-GUARD/ADP/KEL-F
64807	1,331	RUBBER SILICONE CL 1A & 1B GR 50
64810	785	PANEL GL HONEYCOMB
64812	760	MERCURY LAMP
64813	1,535	WIRE HEATER MC363-0031 0038
64814	707	LAMIN EPOXY/PC12-007M COATED
64815	414	CONNECTOR/CABLE
64817	1,503	TUBING VACUFLEX PVC HST
64818	778	MULTI-LAYERED INSULATION GOLDIZED KAPTON/MYLAR/DACRON
64819	778	MULTI-LAYERED INSULATION GOLDIZED KAPTON/MYLAR
64821	616	INSULATION FOAM FLUOREL/URETHANE COATED
64822	1,533	WIRE ELEC TFE/SARAN WRAPPED
64824	406	CONNECTOR DUCTORSEAL 6837/6838
64825	767	MOLD COMPOUND ETHYLENE VINYL ACETAT
64828	403	CONFIG NYLON VELCRO/COTTON
64829	781	MULTI-LAYERED INSULATION TFE/DACRON/AL/MYLAR/POLYESTER
64830	781	MULTI-LAYERED INSULATION TFE/DACRON/AL/MYLAR/NOMEX
64834	404	CONFIG/SEE 20406/20579
64838	779	MULTI-LAYERED INSULATION KAPTON/MYLAR/SILVER FOIL
64840	1,503	TUBING TYGON/L-T-80 TAPE WRAP
64841	589	INK MARKER PEN 2500/PAPER
64842	589	INK MARKER PEN 2500/JCP E20
64845	580	HOSE URINAL SILICONE RUBBER/WIRE
64847	1,483	TUBING CEVOLITE X651
64849	403	CONFIG NYLON VELCRO/COTTON COF
64854	403	CONFIG COMPOSITE SHUTTLE SUIT
64856	795	PENCIL GREASE ON LP4 FILM
64857	795	PENCIL GREASE WITH VELCRO
64858	404	CONFIG SEE 06475/05325
64859	1,484	TUBING DURAPLUS ABS
64861	1,526	WIRE ELEC GWN 1328 AG PLATED
64863	780	MULTI-LAYERED INSULATION TEDLAR/MYLAR/3M838/VELCRO
64864	780	MULTI-LAYERED INSULATION TEDLAR/ALUMINIZED MYLAR
64866	1,442	TAPE PTFE (EXPANDED)
64867	395	COATING YELLOW 33798 PRIMER/EPOXY TOPCOAT
64869	1,282	RUBBER EPMD264
64870	184	ADHESIVE LOCTITE 270
64871	1,475	THREAD CRES 300 SERIES
64872		DELETED SEE 05458
64873	764	MOLD COMPOUND DAP SDG 7717
64874	1,536	WIRE STYLE 2850/SCOTCH 280
64875	116	ADHESIVE EE4215/H3469
64876	166	ADHESIVE FILM FM400
64880	303	CLAMP CABLE P/N 10020-24
64881	558	FLUOROCOMP #103

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006736 0

MATCD	PAGE	DESIGNATION
64883	370	COATING POLYAMIDE EPOXY
64884	370	COATING POLYAMIDE EPOXY
64885	371	COATING POLYIMIDE EPOXY YELLOW TC
64886	307	COATING 02-GY-3 WITH KEVLAR LAMIN
64887	306	COATING 02-GY-3 WITH ARAMID LAMIN
64888	374	COATING POLYURETHANE WHITE
64889	309	COATING 17875 POLYURETHANE WHITE
64892	682	LACING TAPE PTFE/GLASS
64894	1,419	TAPE G400600 .5 MIL TYPE A TEFLON WITH VAC DEPOSIT SILVER WITH VAC DEPOSITED INCONEL WITH 966 ACRYLI C ADHESIV
64895	198	ADHESIVE METLBOND 328
64897	322	COATING A276/02-Y-24
64898	322	COATING A276/P527D
64899	1,419	TAPE G400300 2 MIL TYPE A TEFLON WITH VACUUM DEPOSITED SILVER AND INCONEL
64900	718	LAMIN TEXTOLITE 11546
64901	1,475	THREAD DACRON "FF"
64902	1,475	THREAD DACRON "B"
64903	1,514	WEBBING DACRON
64904	1,515	WEBBING DACRON 900 LB
64906	1,515	WEBBING DACRON 80 LB
64907	1,515	WEBBING DACRON 600 LB
64908	1,514	WEBBING DACRON 280
64909	58	ADHESIVE BSL 208/5 FOAM
64910	1,519	WEBBING NYLON 5000 LB
64912	1,519	WEBBING NYLON 2500 LB
64913	1,519	WEBBING NYLON 2300 LB
64914	1,520	WEBBING NYLON 9000 LB
64915	1,519	WEBBING NYLON 1000 LB
64916	1,513	WEBBING 3600 COND. R
64917	738	LUBE GREASE APIEZON H
64918	1,516	WEBBING KEVLAR 6000 LB
64920	1,516	WEBBING KEVLAR 550 LB
64921	1,516	WEBBING KEVLAR 10000 LB
64922	371	COATING POLYURETHANE BLACK
64923	531	FILM 43/82/2 KAPTON/NOMEX/AU
64924	375	COATING POLYURETHANE YELLOW 33538
64925	372	COATING POLYURETHANE LT GRAY 36622
64926	371	COATING POLYURETHANE BLACK
64927		DELETED SEE 05122
64930	467	FABRIC NARMCO 3200/120
64931	505	FASTENER SCOTCHMATE SJ3400 HOOK
64932	505	FASTENER SCOTCHMATE SJ3401 LOOP
64933	506	FASTENER SCOTCHMATE SJ3402 HOOK
64934	506	FASTENER SCOTCHMATE SJ3509 HA ADHESIVE BACK
64935	507	FASTENER SCOTCHMATE SJ3514 HA ADHESIVE BACK
64936	506	FASTENER SCOTCHMATE SJ3503 PS ADHESIVE BACK
64937	506	FASTENER SCOTCHMATE SJ3504 PS ADHESIVE BACK
64938	506	FASTENER SCOTCHMATE SJ3415 HOOK HS
64939	507	FASTENER SCOTCHMATE SJ3511 HS ADHESIVE BACK
64941		DELETED SEE 20877
64942	752	LUBE OIL FOMBLIN Y140/13
64943	506	FASTENER SCOTCHMATE SJ3418 LOOP FIRE/PR
64944	506	FASTENER SCOTCHMATE SJ3419 HOOK FIRE/PR
64945	507	FASTENER SCOTCHMATE SJ3526 HOOK/26 SER
64946	507	FASTENER SCOTCHMATE SJ3527 LOOP/26 SER
64947	507	FASTENER SCOTCHMATE SJ3528 HOOK/26 SER
64948	507	FASTENER SCOTCHMATE SJ3530 HOOK/36 SER
64949	507	FASTENER SCOTCHMATE SJ3537 LOOP/36 SER
64950	507	FASTENER SCOTCHMATE SJ3538 HOOK/36 SER
64951	506	FASTENER SCOTCHMATE SJ3501 SOL/HA ADHESIVE
64952	506	FASTENER SCOTCHMATE SJ3502 SOL/HA ADHESIVE
64953	507	FASTENER SCOTCHMATE SJ3571 LOOP PS ADHESIVE
64954	508	FASTENER SCOTCHMATE SJ3572 HOOK PS ADHESIVE
64955	507	FASTENER SCOTCHMATE SJ3551 TY 400 PS
64956	507	FASTENER SCOTCHMATE SJ3552 TY 170 PS
64957	506	FASTENER SCOTCHMATE SJ3441 TY 400
64958	506	FASTENER SCOTCHMATE SJ3442 TY 170
64959	507	FASTENER SCOTCHMATE SJ3541 TY 400
64960	507	FASTENER SCOTCHMATE SJ3542 TY 170
64962	644	INSULATION FOAM SYNTACTIC EPON 815
64963	1,476	THREAD KEVLAR SIZE E
64964	419	CORD NYLON
64965	1,501	TUBING TEFLON FEP SMT HS
64968	1,489	TUBING INSULTITE KYNAR HST CLEAR NOC
64969	558	FLUOROGOLD WITH GREEN PIGMENT
64970	738	LUBE GREASE APIEZON T
64971	1,408	SPONGE RUBBER SILICONE PD200-16/RTV560
64972	1,474	THERMOTROL 2122/MG CONTAINER
64973	367	COATING PC17/17M POLYURETHANE
64975	318	COATING 824-408 POLYURETHANE GLOSS ORANGE
64976		DELETED SEE 62059
64977	452	FABRIC FIBERSLIP B40
64978	779	MULTI-LAYERED INSULATION KAPTON/DACRON/A276 COATED
64979	712	LAMIN MELAMINE/GLASS G5-813
64980		DELETED SEE 63235
64981		DELETED SEE 06432
64983	1,315	RUBBER POLYURETHANE X364 RHOPLEX/FLOCC
64984	407	CONNECTOR ELEC G05D170A2BABL
64985	497	FABRIC SILICONE/GLASS SG1M
64986	332	COATING CHEMGLAZE II A471
64987	406	CONNECTOR ELEC 27499E10F99P
64988	408	CONNECTOR ELEC PT06E-10-S5005
64989	406	CONNECTOR ELEC 3476L10-S5
64991	375	COATING PRC NO 1 SEE TEST REPORT
64992	375	COATING PRC NO 2 SEE TEST REPORT
64993	376	COATING PRC NO 3 SEE TEST REPORT
64994	376	COATING PRC NO 4 SEE TEST REPORT
64995	376	COATING PRC NO 5 SEE TEST REPORT
64996	376	COATING PRC NO 6 SEE TEST REPORT
64997	376	COATING PRC NO 7 SEE TEST REPORT
64998	376	COATING PRC NO 8 SEE TEST RPT
64999	377	COATING PRC NO 9 SEE TEST RPT
65000	328	COATING CARBOLINE NO 10 SEE RPT
65001	328	COATING CARBOLINE NO 11 SEE RPT
65002	328	COATING CARBOLINE NO 12 SEE RPT
65003	328	COATING CARBOLINE NO 13 SEE RPT
65004	328	COATING CARBOLINE NO 14 SEE RPT
65005	328	COATING CARBOLINE NO 15 SEE RPT

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006737 2

MATCD	PAGE	DESIGNATION
65006	328	COATING CARBOLINE NO 16 SEE RPT
65007	329	COATING CARBOLINE NO 17 SEE RPT
65008	329	COATING CARBOLINE NO 18 SEE RPT
65009	324	COATING AEROCOAT AR7 SEE REPORT
65010	376	COATING PRC NO 21 SEE TEST RPT
65011	377	COATING PRC22 SEE TEST REPORT
65012	377	COATING PRC23 SEE TEST REPORT
65013	377	COATING PRC24 SEE TEST REPORT
65014	377	COATING PRC25 SEE TEST REPORT
65015	377	COATING PRC26 SEE TEST REPORT
65016	377	COATING PRC27 SEE TEST REPORT
65017	378	COATING PRC28 SEE TEST REPORT
65018	378	COATING PRC29 SEE TEST REPORT
65019	329	COATING CARBOLINE NO 30 SEE RPT
65020	329	COATING CARBOLINE NO 31 SEE RPT
65021	329	COATING CARBOLINE NO 32 SEE RPT
65022	757	MARKER CABLE HT-TMS-CM
65023	292	CABLE ELEC EF-2PWMS HIFLON
65024	1,527	WIRE ELEC KAPTON/FEP SPECIAL
65025	325	COATING ALUMINIZED ENAMEL SEE REPORT
65026	572	HERBICIDE BOROSIL 4 SEE REPORT
65027	1,376	RUBBER VITON GF CPD SEE REPORT
65029	736	LUBE EVERLUBE 620 SEE TEST RPT
65030	1,413	TAPE ANTI-SLIP SAFETY SEE TEST REPORT
65031	571	HEADBAND HEADSET MX2506/AIC
65032	329	COATING CARBOLINE NO 33 SEE RPT
65033	1,512	WALLBOARD/PASTE/SEAMING TAPE
65034	1,513	WALLBOARD/PASTE/TAPE COATED
65035	512	FASTENER VELCRO NOMEX HOOK 66 BACKING 0372
65036	1,446	TAPE SCOTCH 390 POLYETHYLENE
65037	1,400	SILICON CARBIDE ON AL 6061
65038	1,400	SILICON CARBIDE DISCONT ON AL
65039	302	CHEMFABRICS 1
65040	302	CHEMFABRICS 2
65041	303	CHEMFABRICS 3
65042	542	FILM MPD2055 50 GAUGE CF
65043	1,518	WEBBING NOMEX 9960 FR
65045	479	FABRIC NOMEX/DENIM BLUE
65046	476	FABRIC NOMEX S619
65047	780	MULTI-LAYERED INSULATION RADIATION SHIELD
65049		DELETED SEE 62951
65050	621	INSULATION FOAM NCFI 22-65 WITH FRL4
65051	368	COATING PLV2000 HS
65054	742	LUBE GREASE BRAYCOTE 806A
65055	1,527	WIRE ELEC L/N 0000003740
65056	1,384	RUBBER VITON VL1502H285
65057	781	MULTI-LAYERED TFE TAPE/CLAMP
65059	609	INSULATION FOAM CPR488/BX250 WITH CONATHANE
65060	609	INSULATION FOAM CPR488/BX250 WITH EPOXY PRIMER
65061	1,400	SINGLE LAYER TAPE/BENDIX CLAMP
65062	358	COATING IRIDITE 14-2/CHROMATE
65063	326	COATING AR7 WITH KRYTOX 240AC
65064	611	INSULATION FOAM CPR488/ISOCYANURATE
65065	325	COATING AR7 ON KEL-F DISCS
65066	478	FABRIC NOMEX-BLUE WITH FC4101-C16
65067	325	COATING AR7 ON TEFLON TFE DISCS
65069	345	COATING EMRALON 330
65070	741	LUBE GREASE BRAYCOTE 805B2
65071	750	LUBE GREASE TRIBOLUBE 15
65072	746	LUBE GREASE NYE 899
65073	416	CORD KEVLAR 275KOZ3/300 POLYU
65074	1,459	TAPE SCOTCHLITE 8850
65075	1,335	RUBBER SILICONE E6132
65076	390	COATING TRITHERM 981 WIRE ENAMEL
65078	665	LABEL 8084-YG REMOVABLE
65081	394	COATING WHITE EPOXY/H2
65082	283	BATTERY CR2430 3V LITHIUM
65084	522	FASTENER VELCRO NYLON LOOP SJ3418 AND HOOK SJ3419B
65085	592	INK PEN SL SILVER BROAD POINT
65086	539	FILM KAPTON/BETA 107 POLYESTER FR
65087	340	COATING DC 4-77 ENAMEL
65088	1,484	TUBING ELEC PTFE HST DUAL WALL
65089	349	COATING EPOXY POLYAMIDE ON STAINLESS STEEL
65090	1,379	RUBBER VITON O-RING V730-75
65091	1,379	RUBBER VITON O-RING V835-75
65092	1,370	RUBBER VITON 75
65093	1,456	TAPE SCOTCH Y9485
65094	135	ADHESIVE EPON 826/Z
65095	662	KEL-F 81/AR-7
65097	334	COATING CHEMGLAZE Z306/9924
65098	370	COATING POLYAMIDE WITH CHEMGLAZE Z306
65100	340	COATING DC 3140/FLUOREL 7GA
65101	96	ADHESIVE DYMAX 181
65102	96	ADHESIVE DYMAX 602
65103	96	ADHESIVE DYMAX 415
65104	96	ADHESIVE DYMAX 20017
65105	379	COATING PRIMER/CHEMGLAZE A276
65106	583	INK 8447 BLACK
65108	1,377	RUBBER VITON O-RING CPD 16207
65109	1,377	RUBBER VITON O-RING CPD 16129
65110	576	HOSE NEOFAB-2 FLEX
65111	791	PAPER XEROX 4200
65112	687	LAMIN CYCOM 6101-2/7781
65113	369	COATING POLANE F63 VI
65114	475	FABRIC NOMEX S/470 LAUNDERED
65117	535	FILM EKTACHROME 200
65119	325	COATING AR7 ON STEEL DISCS
65121	360	COATING LACQUER BLACK 32178-66
65122	1,325	RUBBER SILICONE 200A
65124	1,527	WIRE ELEC KAPTON/FEP SEE RPT
65125	284	BATTERY LITHIUM LF 1/2W
65126	1,443	TAPE RUBBER FLUOREL L2231
65127	553	FILM TEFLON SILVER COATED
65128	460	FABRIC HT-473-41 NOMEX/COTTON
65129	460	FABRIC HT-472-40 NOMEX/COTTON
65130	492	FABRIC POLYPRO LYCRAL/POLYES
65131	433	FABRIC 100% COTTON KNIT JERSEY
65132	473	FABRIC NOMEX DENIM LAUNDERED
65135	396	COMPOSITE 5245C RESIN/IMG FIBR
65136	725	LUBE DRY 958-301 TEFLON

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006738 4

MATCD	PAGE	DESIGNATION
65137	1,461	TAPE TEFLON FEP
65139	294	CABLE IEEE 488
65140	349	COATING EPOXY POLAMIDE WITH POLYURETHANE OVERCOAT
65141	1,333	RUBBER SILICONE CV1144-0
65142	1,308	RUBBER NITRILE N674-70
65143	461	FABRIC HT-96-62G NOMEX NATURAL
65144	537	FILM HS8171 VAC PAK NYLON
65146	740	LUBE GREASE BRAYCOTE 600
65147	741	LUBE GREASE BRAYCOTE 601 B/L
65148	741	LUBE GREASE BRAYCOTE 804
65149	741	LUBE GREASE BRAYCOTE 804A
65150	741	LUBE GREASE BRAYCOTE 805
65151	741	LUBE GREASE BRAYCOTE 805A
65152	741	LUBE GREASE BRAYCOTE 806
65155	425	DELRIN ACETAL
65156	756	LUBE OIL WD40/M6 SEE REPORT
65158	315	COATING 643-18-1 WHITE
65159	1,277	RUBBER COHRLASTIC 4050 SILICONE GLASS
65161	755	LUBE OIL WD40/LEEDER 241K
65162	137	ADHESIVE EPON 828/DTA 7500 GLASS
65163	539	FILM KAPTON/CHEMGLAZE/BETA 107
65165	1,412	TAPE 925 ALUMINUM WITH POLYESTER ADHESIVE
65166	420	CORD SILVERTON 55-1 ORANGE
65168	958	PLASTIC LEXAN 9600-116 POLYCARBONATE
65169	304	CLAMP CUSHION TEFLON (13K)
65170	427	DISC AL LITHIUM ALLOY
65171	531	FILM 2481 INFRARED (135-36)
65172	775	MULTI-LAYERED INSULATION AL/KAPTON/DACRON/NOMEX/ MYLAR
65173	203	ADHESIVE MVP TY 33
65174	1,377	RUBBER VITON O-RING CPD 19447
65175	370	COATING POLYAMIDE EPOXY PRIMER YELLOW
65176	1,377	RUBBER VITON O-RING 19357
65177	1,470	TEFLON PTFE DISCS
65178	448	FABRIC DUCK FLEX BLUE
65179	447	FABRIC DUCK FLEX BLACK
65180	1,253	POTTING COMPOUND NYLON BOOT
65181	1,380	RUBBER VITON SR2702-72
65182	1,379	RUBBER VITON O-RING S/A2-214
65183	743	LUBE GREASE FOMBLIN Z-LHT
65184	357	COATING INK ON PAPER FROM HP2225A
65185	1,444	TAPE SCOTCH 1181
65186	1,487	TUBING FLUOROELASTOMER HS
65187	727	LUBE DRY DYFLON
65188	748	LUBE GREASE SILICONE GE688
65189		DELETED SEE 05339
65190	574	HOSE FLEX RTV 630
65191	275	ADHESIVE VERSAMID 140
65192	1,251	POTTING COMPOUND EPOXY AP1371 A/B
65193	435	FABRIC ALUMINIZED M11678 NEOPRENE KEVLAR COATED WITH POLYURETHANE OC
65194	465	FABRIC M11673/NYLON/URETHANE
65195	764	MOLD COMPOUND E-21718/X49556
65196	764	MOLD COMPOUND E-21718/X49560
65197	577	HOSE R267/410 SERIES
65198	472	FABRIC NOMEX ARAMID NAVY BLUE
65200	284	BATTERY NI/CD 5/600KZ 6V
65201		DELETED SEE 61999
65202	1,459	TAPE SCOTCHLITE 680 WITH CTRL TAC
65206	394	COATING WATER BASE PRIMER
65207	311	COATING 44-GN-11 EPOXY POLYAMIDE
65208	487	FABRIC PBI 84410-426 BRAID
65210	541	FILM LH94-5 CLEAR
65212	562	GASKET 9-210-6B SILICONE
65213	688	LAMIN EPOXY CL522
65214	1,418	TAPE FLEXITE TGL BLUE ADHESIVE
65215	1,463	TAPE TEFLON THREAD
65217	617	INSULATION FOAM GREAT STUFF WITH FRL-4
65218	617	INSULATION FOAM INSTA FOAM WITH FRL-4
65219	628	INSULATION FOAM POLYISOCYANURATE 2380
65220	629	INSULATION FOAM POLYISOCYANURATE FSC85A11
65221	609	INSULATION FOAM CPR330-32 POLYISOCYANURATE
65222	632	INSULATION FOAM POLYURETHANE FS110 MMC
65223	628	INSULATION FOAM POLYISOCYANURATE 2381A
65224	621	INSULATION FOAM NCFI 23 38 MMC
65225	621	INSULATION FOAM NCFI 23 58 POLYISOCYANURATE
65226	629	INSULATION FOAM POLYISOCYANURATE FSC83A55
65227	629	INSULATION FOAM POLYISOCYANURATE NCFI 23 66
65228	629	INSULATION FOAM POLYISOCYANURATE THR 251
65229	628	INSULATION FOAM POLYISOCYANURATE 1756
65230	624	INSULATION FOAM PDL/BX250 WITH TYBOND
65231	624	INSULATION FOAM PDL/BX250 WITH CONATHANE
65232	624	INSULATION FOAM PDL/BX250 WITH EPOXY PRIMER
65234	645	INSULATION FOAM TEXTHANE 221-25 POLYURETHANE
65235	633	INSULATION FOAM POLYURETHANE P2004
65236	618	INSULATION FOAM ISOCYANURATE AW255
65237	471	FABRIC NOMEX 90043/46
65238	460	FABRIC HT-59-62 NOMEX
65239	460	FABRIC HT-5-42 NOMEX NATURAL
65240	460	FABRIC HT-318-53 NOMEX NATURAL
65241	753	LUBE OIL HALOCARBON 6.3
65244	280	ANTENNA MATL KEV/KAP/EPOXY
65245	532	FILM 8210 WITH 8060 LABEL
65249	537	FILM HS800 VAC PAK NYLON GOLD
65250	96	ADHESIVE DURALCO 700 HIGH TEMP
65251	357	COATING INK 002-0001-01 STAMP
65252	780	MULTI-LAYERED INSULATION RADIATION SHIELD TEFLON
65253	378	COATING PRIMER POLYCLUTCH
65254	773	MOLD COMPOUND TA-88-50
65255	735	LUBE EMRALON 314 A/B
65257	742	LUBE GREASE D840924A T1
65258	683	LACING TAPE T3333
65259	729	LUBE DRY INLOX 88
65260	1,452	TAPE SCOTCH 75-4280-0501-3-8005/ADHESIVE
65261	772	MOLD COMPOUND RX 3-1-530
65263	781	MULTI-LAYERED INSULATION VELCRO/POLYESTER
65264	1,449	TAPE SCOTCH 5453 TFE/SILICONE/GLASS
65265	1,428	TAPE MANCO FIREGUARD FRD60
65266	1,384	SALOX-M
65268	472	FABRIC NOMEX ARAMID 3/0049 6OZ

MSFC-HDBK-527 REV F 9999942 0006739 6

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
65269	535	FILM EKTAPRINT ON E20 PAPER
65271	580	HOSE TEFLON WITH STEEL
65272	747	LUBE GREASE RHEOLUBE 738
65287	557	FLIGHT DATA FILE WITH BOOKS
65288	280	ALCOHOL WIPES HRI8026-4204-0
65291	459	FABRIC HT-318-53 NOMEX
65292	460	FABRIC HT-5-42 NOMEX
65293	640	INSULATION FOAM RENOLSOL RW54-02
65295	618	INSULATION FOAM ISOCYANURATE S16-49
65298	792	PCB CONNECTOR/VALOX 420/RYTON
65299	1	ABLATOR MA-25/FRL-IV
65300	81	ADHESIVE CREST 7344 A/B
65301	618	INSULATION FOAM ISOCYANURATE MO9-58-2
65303	96	ADHESIVE DYMAX 628
65305	1,370	RUBBER VITON 3-916V
65306	1,370	RUBBER VITON 3-912V
65308	1,467	TAPE VITON-FLUOREL/CLAMP
65309	429	ELASTOMER PNF
65310	428	DURA-TUFF #4776
65311	608	INSULATION FOAM CPR1002 POLYURETHANE
65312	531	FILM 8019,8020 WITH 8060 LABEL
65313	717	LAMIN SAFE-T-POXY
65314	1,282	RUBBER EPR 5708
65315	1,304	RUBBER NEOPRENE ZX2002
65317	1,384	RUBBER VITON VL1502H285
65318	1,491	TUBING KYNAR PVF2 HST
65319	1,503	TUBING THERMOFIT S1044 VITON
65327	408	CONNECTOR ELECT GLASS/PHENOLIC
65328	350	COATING EPOXY WHITE TOPCOAT WITH H2 CATALYST
65329	448	FABRIC DURETTE 400-11/7878 NOMEX
65330	1,494	TUBING POLYOLEFIN B322 HST
65331	580	HOSE TITEFLEX CONDUCTIVE
65334	466	FABRIC MOLESKIN
65335	476	FABRIC NOMEX S619/ARAMID GRN
65336	490	FABRIC POLYESTER FILTER
65337	645	INSULATION FOAM TEST TUBE RACK 2610
65338		DELETED SEE 63949
65339	546	FILM NYLON CLEAR 06
65340	303	CLAMP CUSHION FLOUROSILICONE
65341	22	ADHESIVE ABLEFILM 561
65342	1,490	TUBING KYNAR 01744-08 SOLDER SLEEVE
65343	555	FILM XRS1000 AGFA COLOR
65344	780	MULTI-LAYERED INSULATION SLD BLANKETS NON STD TEST
65345	565	GLOVE CLOTH NOMEX RTV 157 GREEN
65347	79	ADHESIVE CONDUCTIVE VERSATAC PAD
65348	472	FABRIC NOMEX ARAMID FR P/N E-2
65350	578	HOSE SILICONE PUROSIL 80-100
65351	578	HOSE SILICONE PUROSIL 70-087
65353	747	LUBE GREASE POLYMER MPG2
65357	492	FABRIC POLYGUARD II
65358	349	COATING EPOXY PRIMER 37051
65360	960	PLASTIC LEXAN MARGARD MR5004-112
65361	669	LABEL STOWAGE LOCATION DES
65362	788	PAPER HP INKJET 92261N
65363	1,362	RUBBER SILICONE SWS845 CAT KX
65364	392	COATING URETHANE AP4004/AP4154
65365	309	COATING 33798 TOPCOAT WITH POLYAMIDE PRIMER
65366	1,505	ULTRA ETHYLUX POLYETHYLENE
65369	1,493	TUBING PLASTIC REINFORCED/CLEAR
65374	265	ADHESIVE TRABOND F1130F117
65376	311	COATING 44-GN-11/CHEMGLAZE A276
65377	348	COATING EPOXY ERLX1964/15274Z6SPQ
65378	451	FABRIC FELT NYLON 236-006-03
65379	1,499	TUBING SILASTIC P/N 601405
65380	790	PAPER SCOTT #60
65381	1,334	RUBBER SILICONE DIMETHYL SILOXANE
65382	1,418	TAPE FIBERGLASS QUIK-TAPE
65383		DELETED SEE 00515
65384		DELETED SEE 05123
65385	399	COMPOUND E4-7.70 GLASS FILLED/BLACK
65386	399	COMPOUND E4-7.68/GLASS/DARK GREY
65387	399	COMPOUND E4-8.97 BLUE
65388	399	COMPOUND E4-7.71 GLASS FILLED/BLACK
65389	399	COMPOUND E4-7.25 GLASS FILLED/GREEN
65390	1,378	RUBBER VITON O-RING S/A 2-212
65391	1,470	TEFLON SAMPLE
65392	6	ADHESIVE 1P20025 EPOXY CLASS 1
65393	304	CLAMP P/N TAS70T08X;4X;6X
65395	1,483	TRUCITE A BLUE
65396	699	LAMIN EPOXY/GLASS STRUCOL R1602
65397	1,388	SEALANT GASK-O-SEAL
65399	342	COATING DER 332/VERSAMID 125
65401	498	FABRIC SPECTRA 900
65402	471	FABRIC NOMEX 863 TWILL
65405	268	ADHESIVE UNISET A359-4 EPOXY
65407	47	ADHESIVE ARON ALPHA 202
65408	750	LUBE GREASE TRIBOLUBE 16
65409	347	COATING ENVIBAR UV1244T
65413	471	FABRIC NOMEX 863/3 TWILL 2X2
65414	553	FILM TEFLON FEP T160
65415	439	FABRIC CHEMSTAT 919 NOMEX
65416	1,502	TUBING THERMOFIT 222D242 HS
65417	1,502	TUBING THERMOFIT 222D253 HS
65419	515	FASTENER VELCRO NYLON HOOK 65
65420	518	FASTENER VELCRO NYLON HOOK 66 NON MELTING ARAMID GROUND
65421	520	FASTENER VELCRO NYLON LOOP 1000
65422	508	FASTENER VELCRO ALL NON MELTING ARAMID LOOP 2000
65423	499	FABRIC TECKNIT 72-08116AG FILL
65425	1,398	SHAVING CREME GEL 5951 D68B
65426	368	COATING PIPE SEALANT ON FIBERGLASS
65428	197	ADHESIVE METALSET A4 EPOXY
65430	1,378	RUBBER VITON O-RING S/A 2-343
65437	1,422	TAPE G408150 5 MIL TEFLON VACUUM DEPOSITED SILVER AND INCONEL WITH 1 MIL SILICONE ADHESIVE
65438	1,420	TAPE G405110 1 MIL KAPTON WITH VACUUM DEPOSITED ALUMINUM
65439	1,420	TAPE G401000 VACUUM DEPOSITED ALUMINUM 1 MIL KAPTON WITH 966 ACRYLIC ADHESIVE
65441	249	ADHESIVE SILICONE DC999

MSFC-HDBK-527 REV F 9999942 0006740 2

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
65442	250	ADHESIVE SILICONE SILITE 17150
65443	1,414	TAPE C666
65444	1,316	RUBBER RTV 577/T-12/SS4415/A276
65445	330	COATING CHEMGLAZE A276/9924 PRIMER
65446		DELETED SEE 06236
65447	458	FABRIC GORTEX P/N L11517
65448	1,338	RUBBER SILICONE MDX4-4210 MEDICAL GRADE
65449	330	COATING CHEMGLAZE A276/KOROPON
65450	1,484	TUBING ECC POLYOLEFIN HS
65451	526	FASTENER VELCRO POLYESTER LOOP 192822/HOOK 192832
65453	1,427	TAPE LATEX ST10
65454	353	COATING GRAY PAINT SEE TEST RPT
65455	1,452	TAPE SCOTCH 8210 LABEL GUARD
65456	665	LABEL 8060 PLASTIC/POLYESTER BASE
65457	1,421	TAPE G406520 2 MIL TEFLON WITH 966 ACRYLIC ADHESIVE
65458	527	FASTENER VELCRO STILAN POLYESTER HOOK/ASTRO
65459	613	INSULATION FOAM DENSITE 4 GUARDIAN/G 8003
65460	1,488	TUBING HEAT SHRINKABLE
65461	1,408	SPONGE RUBBER SILICONE KE901FU
65462	290	CABLE COAX RG188
65463	1,378	RUBBER VITON O-RING S/A 2-024
65464	1,378	RUBBER VITON O-RING S/A 2-016
65465	1,378	RUBBER VITON O-RING S/A 2-012
65466	1,378	RUBBER VITON O-RING S/A 2-014
65467	1,378	RUBBER VITON O-RING S/A 2-020
65468	1,378	RUBBER VITON O-RING S/A 2-035
65470	659	INSULATION WIRE SILICONE J-SIL39013
65471	95	ADHESIVE DOUBLE/BUBBLE EPOXY
65472	662	KEL-F 81/6061 RESIN
65473	1,500	TUBING SPECIAL FLEX KYNAR K2
65474	1,483	TUBING BEN-HAR VITON 44
65476	1,504	TUBING VARGLASS VITON 231
65477	750	LUBE GREASE TRIBOLUBE 15MS
65478	750	LUBE GREASE TRIBOLUBE 15RP
65480	556	FILTER WRATTEN GELATIN 29
65481	563	GASKET RING FC-195
65482	563	GASKET RING FC-192
65483	563	GASKET RING FC-171
65484	563	GASKET RING GSF-1100
65485	389	COATING TEMP CONTROL POLYURETHANE/AL
65489	1,502	TUBING TEKFIT A222003 HS BLACK
65490	303	CLAMP CUSHION TA101
65492	505	FASTENER SCOTCHMATE DUAL LOCKING TY 400
65493	1,465	TAPE TEMP-R-TAPE K350SP
65495	592	INK PEN 775SL SILVER MED-PT
65496	440	FABRIC COTTON AIRC84410-502/FR
65498		DELETED SEE 20049
65499	1,271	RUBBER BUNA N FC776
65500	468	FABRIC NOMEX 0049 6OZ FP/WP
65501	810	PLASTIC ACETAL
65502	89	ADHESIVE DEVCON ALUMINUM PUTTY
65503	1,534	WIRE ELEC WITH POLYIMIDE INSULATION
65504	637	INSULATION FOAM PYRELL WITH REFSET COATING
65512	112	ADHESIVE ECCOBOND 83C EPOXY
65513	641	INSULATION FOAM SCOTTFELT INSULATION
65515		DELETED SEE 65514
65516		DELETED SEE 65514
65517		DELETED SEE 65514
65520	1,426	TAPE L-T-90D/SCOTCH 800
65521	1,466	TAPE THERMOSET
65522	1,439	TAPE PLASTIC
65523	175	ADHESIVE HE17017 E-Z KIT
65524	1,493	TUBING POLYESTER HST
65525	1,421	TAPE G406510 1 MIL TEFLON WITH 966 ACRYLIC ADHESIVE
65526	375	COATING PR484TC/PR475S/PR19 PR
65527	1,493	TUBING PLASTIC
65529		DELETED SEE 61618
65530	50	ADHESIVE BIPAX TRADUCT BB2902
65531	754	LUBE OIL KILOPOISE
65532	736	LUBE EMRALON 320 A/B
65533	662	KEL-F 81/6060 RESIN
65534	503	FABRICOAT SRGA-0209
65535		DELETED SEE 65261
65536	22	ADHESIVE ABLEFILM 561/40% FILLED
65537	334	COATING CHEMGLAZE Z302/9922 PRIMER
65538	334	COATING CHEMGLAZE Z302/9924 PRIMER
65539	333	COATING CHEMGLAZE Z302/02-GN-40PRIMER
65540	334	COATING CHEMGLAZE Z306/9922 PRIMER
65541		DELETED SEE 65097
65542	334	COATING CHEMGLAZE Z306/02-GN-40 PRIMER
65543	423	CU CLAD FR4/PCB WITH MS-470 COATING
65544	608	INSULATION FOAM CPR1061 WITH ALBI COTE COATING
65547	406	CONNECTOR ELEC 27508E12F35P
65548	704	LAMIN EPOXY/GRAPHITE T50/934
65549	1,529	WIRE ELEC POLYIMIDE INSULATION
65552	333	COATING CHEMGLAZE Z302
65553	330	COATING CHEMGLAZE A276/02-GN-40 PRIMER
65554		DELETED SEE 62765
65555	320	COATING 856-204 TFE GREEN/851-255 TFE BLACK/850-204 TFE GREEN PRIMER
65560	8	ADHESIVE 3C #204
65561	8	ADHESIVE 3C #DW 205
65562	8	ADHESIVE 3C PAN-L-BOND
65563	8	ADHESIVE 3C #202
65564	8	ADHESIVE 3C #203
65565	8	ADHESIVE 3C NONETCH FOAM
65566	8	ADHESIVE 3C #27
65567	8	ADHESIVE 3C STYROBOND
65568	8	ADHESIVE 3C WALLBOND
65569	15	ADHESIVE ABLEBOND 16-1
65570	16	ADHESIVE ABLEBOND 161-3
65571	16	ADHESIVE ABLEBOND 163-4
65572	16	ADHESIVE ABLEBOND 184-1
65573	16	ADHESIVE ABLEBOND 190-3
65574	16	ADHESIVE ABLEBOND 190-8
65575	16	ADHESIVE ABLEBOND 224-1
65576	17	ADHESIVE ABLEBOND 342-13 ACC
65577	17	ADHESIVE ABLEBOND 342-3

MSFC-HDBK-527 REV F 9999942 0006741 4

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
65578	17	ADHESIVE ABLEBOND 380-5
65579	17	ADHESIVE ABLEBOND 408-3
65580	17	ADHESIVE ABLEBOND 410-1
65581	18	ADHESIVE ABLEBOND 58-1
65582	18	ADHESIVE ABLEBOND 601-1C
65583	18	ADHESIVE ABLEBOND 606-2
65584	18	ADHESIVE ABLEBOND 66-1
65585	18	ADHESIVE ABLEBOND 681-14
65586	18	ADHESIVE ABLEBOND 69-5
65587	18	ADHESIVE ABLEBOND 71-1LMI
65588	18	ADHESIVE ABLEBOND 724-14C
65589	19	ADHESIVE ABLEBOND 77-1
65590	19	ADHESIVE ABLEBOND 789-3
65591	19	ADHESIVE ABLEBOND 789-4
65592	19	ADHESIVE ABLEBOND 826-1
65593	19	ADHESIVE ABLEBOND 84-1A
65594	19	ADHESIVE ABLEBOND 84-1LMI
65595	20	ADHESIVE ABLEBOND 84-3
65596	20	ADHESIVE ABLEBOND 843-1
65597	20	ADHESIVE ABLEBOND 843-4
65598	20	ADHESIVE ABLEBOND 868-3
65599	20	ADHESIVE ABLEBOND 877-1
65600	20	ADHESIVE ABLEBOND 88-1
65601	20	ADHESIVE ABLEBOND 883-1
65602	20	ADHESIVE ABLEBOND 883-4
65603	20	ADHESIVE ABLEBOND 931-1
65604	20	ADHESIVE ABLEBOND 933-1
65605	21	ADHESIVE ABLEBOND 941-3
65606	21	ADHESIVE ABLEBOND 957-2
65607	21	ADHESIVE ABLEBOND ECF564A
65608	21	ADHESIVE ABLEFILM 517
65609	22	ADHESIVE ABLEFILM 550K
65610	22	ADHESIVE ABLEFILM 561K
65611	23	ADHESIVE ABLEFILM 564A
65612	23	ADHESIVE ABLEFILM ECF550
65613	23	ADHESIVE ABLEFILM ECF561
65614	23	ADHESIVE ABLETHERM 8-2
65615	20	ADHESIVE ABLEBOND 862-7
65616	97	ADHESIVE E-SOLDER 3012
65617	97	ADHESIVE E-SOLDER 3017
65618	97	ADHESIVE E-SOLDER 3021
65619	97	ADHESIVE E-SOLDER 3022
65620	97	ADHESIVE E-SOLDER 3025
65621	97	ADHESIVE E-SOLDER 3026
65622	98	ADHESIVE E-SOLDER 3044
65623	98	ADHESIVE E-SOLDER 3056
65624	98	ADHESIVE E-SOLDER 3069
65625	98	ADHESIVE E-SOLDER 3083
65626	98	ADHESIVE E-SOLDER 320S
65627	191	ADHESIVE MARASET RESIN 532C
65628	191	ADHESIVE MARASET RESIN 532F
65629	191	ADHESIVE MARASET RESIN 536
65630	191	ADHESIVE MARASET RESIN 537
65631	77	ADHESIVE CONCRESIVE
65632	403	CONCRESIVE 1001
65633	403	CONCRESIVE 1001 LPL
65634	77	ADHESIVE CONCRESIVE 1064
65635	77	ADHESIVE CONCRESIVE 1170
65636	77	ADHESIVE CONCRESIVE 1305
65637	78	ADHESIVE CONCRESIVE 1310
65638	78	ADHESIVE CONCRESIVE 1411
65639	78	ADHESIVE CONCRESIVE 1419
65640	78	ADHESIVE CONCRESIVE 1422
65641	78	ADHESIVE CONCRESIVE 1438
65642	78	ADHESIVE CONCRESIVE 1440
65643	78	ADHESIVE CONCRESIVE 1441
65644	78	ADHESIVE CONCRESIVE 3007
65645	78	ADHESIVE CONCRESIVE 3008
65646	78	ADHESIVE CONCRESIVE 3009
65647	403	CONCRESIVE 3012
65648	78	ADHESIVE CONCRESIVE 3013
65649	78	ADHESIVE CONCRESIVE 3014
65650	78	ADHESIVE CONCRESIVE 3034
65651	78	ADHESIVE CONCRESIVE 3042 PENSEAL 50
65652	79	ADHESIVE CONCRESIVE AEX1470
65653	79	ADHESIVE CONCRESIVE AEX1539G
65654	403	CONCRESIVE AEX 1482-0
65655	79	ADHESIVE CONCRESIVE AEX1482X
65656	79	ADHESIVE CONCRESIVE AEX1533G
65657	79	ADHESIVE CONCRESIVE GLOSSFIX 1409
65658	403	CONCRESIVE 1442
65659	6	ADHESIVE 286
65660	10	ADHESIVE 626N
65661	9	ADHESIVE 501 NEOPRENE
65662	34	ADHESIVE AP1400
65663	34	ADHESIVE AP2108
65664	35	ADHESIVE AP2110
65665	35	ADHESIVE AP2118 HI-TEMP
65666	35	ADHESIVE AP2120 HI-TEMP
65667	35	ADHESIVE AP2400 QUICK SET
65668	35	ADHESIVE AP2410 QUICK SET
65669	226	ADHESIVE QUANTUM 701
65670	226	ADHESIVE QUANTUM 702
65671	226	ADHESIVE QUANTUM 703
65672	232	ADHESIVE RUBBER SILICONE RTV 1473
65673	232	ADHESIVE RUBBER SILICONE RTV 157
65674	232	ADHESIVE RUBBER SILICONE RTV 158
65675	11	ADHESIVE 810 OIL/GRIP
65676	97	ADHESIVE DYMAX 828 OIL/GRIP
65677	97	ADHESIVE DYMAX 832 OIL/GRIP
65678	429	DYMAX 840 OIL/GRIP
65679	97	ADHESIVE DYMAX 845 OIL/GRIP
65680	97	ADHESIVE DYMAX 847 OIL/GRIP
65681	57	ADHESIVE BR624
65682	57	ADHESIVE BR626
65683	57	ADHESIVE BR662
65684	166	ADHESIVE FILM FM33
65685	166	ADHESIVE FILM FM40
65686	167	ADHESIVE FILM FM404
65687	167	ADHESIVE FILM FM43

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006742 6

NON-METALS DESIGNATIONS BY MATERIAL CODE

MATCD	PAGE	DESIGNATION
65688	166	ADHESIVE FILM FM34B-18
65689	166	ADHESIVE FILM FM34B-184
65690	167	ADHESIVE FILM FXM250
65691	165	ADHESIVE FILM FM150-2 LP15
65692	165	ADHESIVE FILM FM150-2U
65693	797	PLASTIC 13N/680
65694	167	ADHESIVE FILM FM96 STRUCTURAL
65695	167	ADHESIVE FILM FM96U STRUCTURAL
65696	166	ADHESIVE FILM FM36
65697	165	ADHESIVE FILM FM30
65698	166	ADHESIVE FILM FM32
65699	26	ADHESIVE AMICON A329-1
65700	27	ADHESIVE AMICON C110
65701	27	ADHESIVE AMICON C115
65702	27	ADHESIVE AMICON C120
65703	28	ADHESIVE AMICON C928-46
65704	28	ADHESIVE AMICON CS489
65705	28	ADHESIVE AMICON CS489-2
65706	29	ADHESIVE AMICON T1206
65707	29	ADHESIVE AMICON T426
65708	27	ADHESIVE AMICON C770-4
65709	27	ADHESIVE AMICON C770-5
65710	27	ADHESIVE AMICON C805
65711	27	ADHESIVE AMICON C850-16
65712	27	ADHESIVE AMICON C850-5
65713	27	ADHESIVE AMICON C850-5A
65714	27	ADHESIVE AMICON C850-6
65715	27	ADHESIVE AMICON C868-1
65716	28	ADHESIVE AMICON C929-72-9
65717	28	ADHESIVE AMICON C930-55-2
65718	28	ADHESIVE AMICON C932-46
65719	28	ADHESIVE AMICON C932-62-1
65720	28	ADHESIVE AMICON C940-7
65721	27	ADHESIVE AMICON C840
65722	28	ADHESIVE AMICON G843
65723	28	ADHESIVE AMICON ME5146
65724	28	ADHESIVE AMICON ME778-6
65725	28	ADHESIVE AMICON ME785
65726	28	ADHESIVE AMICON ME845-3
65727	28	ADHESIVE AMICON ME855-2
65728	29	ADHESIVE AMICON ME865-1
65729	29	ADHESIVE AMICON ME868-2
65730	29	ADHESIVE AMICON ME930-12-4
65731	29	ADHESIVE AMICON ME932-44
65732	29	ADHESIVE AMICON SC110
65733	29	ADHESIVE AMICON SC130
65734	29	ADHESIVE AMICON SC130-3
65735	29	ADHESIVE AMICON SC17
65736	29	ADHESIVE AMICON TG86
65737	29	ADHESIVE AMICON TG86EC
65738	29	ADHESIVE AMICON TG86TC
65739	267	ADHESIVE UNISET 108B
65740	267	ADHESIVE UNISET 3663
65741	267	ADHESIVE UNISET 927-10
65742	267	ADHESIVE UNISET A304-6
65743	267	ADHESIVE UNISET A312
65744	268	ADHESIVE UNISET A316-34
65745		DELETED SEE 65699
65746	268	ADHESIVE UNISET A410-10
65747	268	ADHESIVE UNISET D272
65748	268	ADHESIVE UNISET D275
65749	268	ADHESIVE UNISET D275-5
65750	269	ADHESIVE UNISET D276
65751	269	ADHESIVE UNISET D778
65752	269	ADHESIVE UNISET D969
65753	269	ADHESIVE UNISET E131
65754	269	ADHESIVE UNISET E151-3
65755	269	ADHESIVE UNISET E154
65756	269	ADHESIVE UNISET E565
65757	269	ADHESIVE UNISET G500
65758	269	ADHESIVE UNISET G508
65759	269	ADHESIVE UNISET G508-1
65760	269	ADHESIVE UNISET G582
65761	269	ADHESIVE UNISET G583
65762	269	ADHESIVE UNISET G757-1
65763	269	ADHESIVE UNISET G804-3
65764	270	ADHESIVE UNISET G843
65765	270	ADHESIVE UNISET SE613
65766	270	ADHESIVE UNISET SE615
65767	270	ADHESIVE UNISET SE616
65768	270	ADHESIVE UNISET SE617
65769	270	ADHESIVE UNISET SE628
65770	270	ADHESIVE UNISET SE629
65771	270	ADHESIVE UNISET SE630
65772	270	ADHESIVE UNISET SE906-21
65773	270	ADHESIVE UNISET T1207
65774	270	ADHESIVE UNISET T1316
65775	270	ADHESIVE UNISET T219
65776	270	ADHESIVE UNISET T4009
65777	271	ADHESIVE UNISET T597
65778	271	ADHESIVE UNISET T661
65779	271	ADHESIVE UNISET T665
65780	271	ADHESIVE UNISET T920-2
65781	271	ADHESIVE UNISET XT116-1 WITH B71
65782	271	ADHESIVE UNISET XT1203-4 WITH B71
65783	271	ADHESIVE UNISET XT2526
65784	271	ADHESIVE UNISET X2551
65785	271	ADHESIVE UNISET XT4064-3 WITH B100
65786	271	ADHESIVE UNISET XT5012
65787	271	ADHESIVE UNISET XT5066
65788	275	ADHESIVE UV990-24-11
65789	278	ADHESIVE XLC C860-1
65790	29	ADHESIVE AMICON SLC C860-2
65791	278	ADHESIVE XLC C940-2
65792	278	ADHESIVE XLC C940-4
65793	279	ADHESIVE XT5235
65794	39	ADHESIVE AREMCOBOND 515
65795	39	ADHESIVE AREMCOBOND 525
65796	39	ADHESIVE AREMCOBOND 526
65797	40	ADHESIVE AREMCOBOND 556

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006743 8 ■

MATCD	PAGE	DESIGNATION
65798	40	ADHESIVE AREMCOBOND 561
65799	40	ADHESIVE AREMCOBOND 568
65800	40	ADHESIVE AREMCOBOND 570
65801	66	ADHESIVE CERAMABOND 552
65802	66	ADHESIVE CERAMABOND 569
65803	82	ADHESIVE CRYSTALBOND 509 TEMPORARY WASH-AWAY
65804	82	ADHESIVE CRYSTALBOND 555 TEMPORARY WASH-AWAY
65805	82	ADHESIVE CRYSTALBOND 590 TEMPORARY WASH-AWAY
65806	174	ADHESIVE GRAPHIBOND 551A
65807	174	ADHESIVE GRAPHIBOND 551R
65808	226	ADHESIVE PYROBOND 566
65809	226	ADHESIVE PYROPUTTY 600
65810	66	ADHESIVE CERAMABOND 618
65811	41	ADHESIVE ARMSTRONG A12-2
65812	41	ADHESIVE ARMSTRONG A12-3
65813	41	ADHESIVE ARMSTRONG A12/T
65814	41	ADHESIVE ARMSTRONG A2/A
65815	41	ADHESIVE ARMSTRONG A2/H20
65816	41	ADHESIVE ARMSTRONG A2/W
65817	41	ADHESIVE ARMSTRONG A271
65818	41	ADHESIVE ARMSTRONG A3/A
65819	42	ADHESIVE ARMSTRONG A3/E
65820	42	ADHESIVE ARMSTRONG A31
65821	42	ADHESIVE ARMSTRONG A36
65822	42	ADHESIVE ARMSTRONG A39
65823	42	ADHESIVE ARMSTRONG A40
65824	42	ADHESIVE ARMSTRONG A6/A
65825	42	ADHESIVE ARMSTRONG A6/E
65826	42	ADHESIVE ARMSTRONG A6/H20
65827	42	ADHESIVE ARMSTRONG A66
65828	43	ADHESIVE ARMSTRONG A706
65829	43	ADHESIVE ARMSTRONG A708
65830	43	ADHESIVE ARMSTRONG A702
65831	43	ADHESIVE ARMSTRONG C1/A
65832	44	ADHESIVE ARMSTRONG C1/E
65833	44	ADHESIVE ARMSTRONG C3/A
65834	44	ADHESIVE ARMSTRONG C3/E
65835	44	ADHESIVE ARMSTRONG C4/W
65836	47	ADHESIVE ARMSTRONG X81/E
65837	44	ADHESIVE ARMSTRONG C4/D
65838	44	ADHESIVE ARMSTRONG C7/H20
65839	44	ADHESIVE ARMSTRONG C7/W1
65840	44	ADHESIVE ARMSTRONG C7/W2
65841	44	ADHESIVE ARMSTRONG C7/W3
65842	40	ADHESIVE ARMSTRONG 529
65843	44	ADHESIVE ARMSTRONG D218 INDUSTRIAL
65844	44	ADHESIVE ARMSTRONG D222 INDUSTRIAL
65845	45	ADHESIVE ARMSTRONG D234 CONTACT
65846	45	ADHESIVE ARMSTRONG D283 INDUSTRIAL
65847	45	ADHESIVE ARMSTRONG D284
65848	45	ADHESIVE ARMSTRONG D500 CONTACT
65849	45	ADHESIVE ARMSTRONG F1450 PANEL AND WALLBOARD
65850		DELETED SEE 20103
65851	45	ADHESIVE ARMSTRONG J1177 GREY
65852	45	ADHESIVE ARMSTRONG J1188 INDUSTRIAL
65853	45	ADHESIVE ARMSTRONG J1199 TP INDUSTRIAL PART A
65854	45	ADHESIVE ARMSTRONG J1199 TP INDUSTRIAL PART B
65855	45	ADHESIVE ARMSTRONG N111 INDUSTRIAL
65856	45	ADHESIVE ARMSTRONG N117 INDUSTRIAL
65857	45	ADHESIVE ARMSTRONG N122
65858	46	ADHESIVE ARMSTRONG S1200 CONTACT
65859	46	ADHESIVE ARMSTRONG S139 TILE-ON
65860	46	ADHESIVE ARMSTRONG S140 GLAZECRAFT WALLTILE
65861	46	ADHESIVE ARMSTRONG S200 A/B
65862	46	ADHESIVE ARMSTRONG S235 MULTIPURPOSE
65863	46	ADHESIVE ARMSTRONG S252 PAVIMAR
65864	46	ADHESIVE ARMSTRONG S280
65865	46	ADHESIVE ARMSTRONG S285 WALLBASE
65866	46	ADHESIVE ARMSTRONG S553 SEAMSEALING
65867	46	ADHESIVE ARMSTRONG S580
65868	46	ADHESIVE ARMSTRONG S665 TROWELABLE INTERFLEX
65869	46	ADHESIVE ARMSTRONG S670 LATEX INTERFLEX
65870	46	ADHESIVE ARMSTRONG S700 TILE BRUSH-ON
65871	46	ADHESIVE ARMSTRONG S750 TILE ROLL-ON
65872	47	ADHESIVE ARMSTRONG S821 SEAMSEALING
65873	47	ADHESIVE ARMSTRONG S89 TILE
65874	47	ADHESIVE ARMSTRONG S90 TILE
65875	14	ADHESIVE AA1104MB
65876	14	ADHESIVE AA1104RB
65877	47	ADHESIVE AROSET 1044Z40
65878	47	ADHESIVE AROSET 1051Z45
65879	47	ADHESIVE AROSET 1081Z45
65880	47	ADHESIVE AROSET 1214C30
65881	47	ADHESIVE AROSET 1612Z35
65882	48	ADHESIVE AROSET 1832Z1-35
65883	48	ADHESIVE AROSET 1857Z34
65884	48	ADHESIVE AROSET 1910TH52
65885	48	ADHESIVE AROSET 2020W50
65886	48	ADHESIVE AROSET 2510W62
65887	48	ADHESIVE AROSET 2520W60
65888	218	ADHESIVE PLIOGRIP 6000
65889	218	ADHESIVE PLIOGRIP 6600
65890	218	ADHESIVE PLIOGRIP 6627
65891	218	ADHESIVE PLIOGRIP 6800
65892	155	ADHESIVE EPOXYBOND PUTTY
65893	26	ADHESIVE ALLABOND 20/20
65894	79	ADHESIVE CONDUCTING 20/20
65895	160	ADHESIVE FA1
65896	160	ADHESIVE FA14
65897	160	ADHESIVE FA21
65898	160	ADHESIVE FA8
65899	162	ADHESIVE FFA2
65900	162	ADHESIVE FFA5
65901	162	ADHESIVE FFA9
65902	167	ADHESIVE FLEXOBOND 329
65903	167	ADHESIVE FLEXOBOND 423
65904	167	ADHESIVE FLEXOBOND 425
65905	179	ADHESIVE JR228-1
65906	179	ADHESIVE JR228A
65907	182	ADHESIVE LGA1

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006744 T

MATCD	PAGE	DESIGNATION
65908	181	ADHESIVE LCA127
65909	181	ADHESIVE LCA12XM
65910	181	ADHESIVE LCA14
65911	181	ADHESIVE LCA20
65912	181	ADHESIVE LCA21
65913	181	ADHESIVE LCA24
65914	181	ADHESIVE LCA4
65915	181	ADHESIVE LCA4LV
65916	181	ADHESIVE LCA9
65917	233	ADHESIVE SC12
65918	10	ADHESIVE 6603
65919	4	ADHESIVE 117
65920	10	ADHESIVE 7820/20
65921	10	ADHESIVE 6607
65922	4	ADHESIVE 1117
65923	4	ADHESIVE 1137-1
65924	5	ADHESIVE 1515-1
65925	7	ADHESIVE 306
65926	277	ADHESIVE WELDWOOD ALL WEATHER OUTDOOR CARPET
65927	277	ADHESIVE WELDWOOD CARPET CEMENT
65928	277	ADHESIVE WELDWOOD MULTIPURPOSE FLOOR
65929	277	ADHESIVE WELDWOOD WALLCOVERING
65930	84	ADHESIVE DAP 2000 CONSTRUCTION
65931	84	ADHESIVE DAP 4000 SUB FLOOR AND PLYWOOD
65932	277	ADHESIVE WELDWOOD ACRYLIC LATEX CONTACT CEMENT
65933	277	ADHESIVE WELDWOOD ORIGINAL CONTACT CEMENT
65934	11	ADHESIVE 999 CONSTRUCTION
65935	84	ADHESIVE DAP GLUE STICK
65936	85	ADHESIVE DAPTAK REUSABLE
65937	84	ADHESIVE DAP PERMABOND SUPER GLUE FOR WOOD AND LEATHER
65938	84	ADHESIVE DAP PERMABOND SUPER GLUE
65939	277	ADHESIVE WELDWOOD CONTACT CEMENT
65940	277	ADHESIVE WELDWOOD RUBBER MENDER
65941	797	PLASTIC 13N/HH5
65942	79	ADHESIVE CRAFTER'S FAST EPOXY
65943	79	ADHESIVE CRAFTER'S EPOXY
65944	277	ADHESIVE WELDWOOD HEAVY DUTY WALLCOVERING
65945	191	ADHESIVE MAINTZ N1000
65946	278	ADHESIVE WESTAC 718
65947	129	ADHESIVE EPISEAL PLUS
65948	128	ADHESIVE EPISEAL 10-10
65949	129	ADHESIVE EPISEAL 5 MINUTE EPOXY
65950	129	ADHESIVE EPISEAL IRON PUTTY
65951	219	ADHESIVE POLYCO 117-55
65952	219	ADHESIVE POLYCO 2113
65953	219	ADHESIVE POLYCO 2116
65954	219	ADHESIVE POLYCO 2123
65955	219	ADHESIVE POLYCO 2142
65956	219	ADHESIVE POLYCO 2149
65957	219	ADHESIVE POLYCO 2150
65958	219	ADHESIVE POLYCO 2186
65959	219	ADHESIVE POLYCO 571
65960	52	ADHESIVE BOSTIK 1007
65961	53	ADHESIVE BOSTIK 1015
65962	53	ADHESIVE BOSTIK 1076
65963	53	ADHESIVE BOSTIK 1096
65964	53	ADHESIVE BOSTIK 1101
65965	53	ADHESIVE BOSTIK 1142
65966	53	ADHESIVE BOSTIK 1205
65967	53	ADHESIVE BOSTIK 1252
65968	53	ADHESIVE BOSTIK 1315
65969	53	ADHESIVE BOSTIK 1372
65970	53	ADHESIVE BOSTIK 1376
65971	53	ADHESIVE BOSTIK 1398
65972	54	ADHESIVE BOSTIK 1515
65973	54	ADHESIVE BOSTIK 1530
65974	54	ADHESIVE BOSTIK 1600
65975	54	ADHESIVE BOSTIK 2009
65976	54	ADHESIVE BOSTIK 2315
65977	54	ADHESIVE BOSTIK 2363
65978	54	ADHESIVE BOSTIK 2378
65979	54	ADHESIVE BOSTIK 2425
65980	54	ADHESIVE BOSTIK 4025
65981	54	ADHESIVE BOSTIK 4101
65982	55	ADHESIVE BOSTIK 4165
65983	55	ADHESIVE BOSTIK 4252
65984	55	ADHESIVE BOSTIK 4342
65985	55	ADHESIVE BOSTIK 6323
65986	55	ADHESIVE BOSTIK 6330
65987	55	ADHESIVE BOSTIK 6368
65988	55	ADHESIVE BOSTIK 7008
65989	55	ADHESIVE BOSTIK 7431
65990	55	ADHESIVE BOSTIK 7432
65991	55	ADHESIVE BOSTIK 7433
65992	56	ADHESIVE BOSTIK 7434
65993	56	ADHESIVE BOSTIK 7435
65994	56	ADHESIVE BOSTIK 8230
65995	56	ADHESIVE BOSTIK 8323
65996	56	ADHESIVE BOSTIK 8330
65997	56	ADHESIVE BOSTIK 8363
65998	56	ADHESIVE BOSTIK 8375
65999	56	ADHESIVE BOSTIK 8376
66000	56	ADHESIVE BOSTIK 8377
66001	56	ADHESIVE BOSTIK 8378
66002	56	ADHESIVE BOSTIK 8379
66003	258	ADHESIVE THERMOGRIP 6363
66004	61	ADHESIVE CASTALL 1520/HT70
66005	61	ADHESIVE CASTALL 1520/RT 1
66006	61	ADHESIVE CASTALL 1520/RT 7
66007	62	ADHESIVE CASTALL A343
66008	60	ADHESIVE CASTALL 110 A/B
66009	61	ADHESIVE CASTALL 2009
66010	61	ADHESIVE CASTALL 310 A/B
66011	61	ADHESIVE CASTALL 341
66012	61	ADHESIVE CASTALL 4874
66013	62	ADHESIVE CASTALL 6612
66014	62	ADHESIVE CASTALL D
66015	62	ADHESIVE CASTALL E
66016	63	ADHESIVE CASTALL F

MSFC-HDBK-527 REV F ■ 9999942 0006745 1 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
66017	63	ADHESIVE CASTALL G
66018	64	ADHESIVE CASTALL H
66019	64	ADHESIVE CASTALL J/RT 1
66020	64	ADHESIVE CASTALL J/RT 7A
66021	61	ADHESIVE CASTALL 4875
66022	62	ADHESIVE CASTALL E100
66023	62	ADHESIVE CASTALL E105
66024	62	ADHESIVE CASTALL E106
66025	62	ADHESIVE CASTALL E300
66026	62	ADHESIVE CASTALL E301
66027	62	ADHESIVE CASTALL E301AD
66028	62	ADHESIVE CASTALL E301KT
66029	62	ADHESIVE CASTALL E341
66030	63	ADHESIVE CASTALL E401
66031	63	ADHESIVE CASTALL E403
66032	63	ADHESIVE CASTALL E409
66033	63	ADHESIVE CASTALL E480 A
66034	63	ADHESIVE CASTALL E482 A
66035	63	ADHESIVE CASTALL E483 A
66036	64	ADHESIVE CASTALL K/RT 7A HI-IMPACT EPOXY
66037		DELETED SEE 66036
66038	64	ADHESIVE CASTALL J/E34
66039	64	ADHESIVE CASTALL QUICK CURE
66040	62	ADHESIVE CASTALL E1530/E34
66041	63	ADHESIVE CASTALL E341FR
66042	63	ADHESIVE CASTALL E435/E34
66043	63	ADHESIVE CASTALL E463/E34
66044	63	ADHESIVE CASTALL E464/E34
66045	63	ADHESIVE CASTALL E466/E34
66046	63	ADHESIVE CASTALL E492/E34 FR
66047	64	ADHESIVE CASTALL K/E34
66048	65	ADHESIVE CASTALL U2008
66049	66	ADHESIVE CASTALL U2044
66050	65	ADHESIVE CASTALL U2032
66051	64	ADHESIVE CASTALL U2006
66052	65	ADHESIVE CASTALL U2017
66053	197	ADHESIVE METLBOND 1113
66054	198	ADHESIVE METLBOND 329-7
66055	67	ADHESIVE CERMALLOY 5100
66056	67	ADHESIVE CERMALLOY 5200
66057	67	ADHESIVE CERMALLOY 5200F
66058	67	ADHESIVE CERMALLOY 5300
66059	67	ADHESIVE CERMALLOY 5500
66060	67	ADHESIVE CERMALLOY PC200S
66061	68	ADHESIVE CERMALLOY PC300S
66062	68	ADHESIVE CERMALLOY T2100T
66063	68	ADHESIVE CERMALLOY T2110
66064	68	ADHESIVE CERMALLOY T2110T
66065	68	ADHESIVE CERMALLOY T2200
66066	68	ADHESIVE CERMALLOY T2210
66067	68	ADHESIVE CERMALLOY T2300
66068	68	ADHESIVE CERMALLOY T2310
66069	68	ADHESIVE CERMALLOY T2800
66070	68	ADHESIVE CERMALLOY T2810
66071	68	ADHESIVE CERMALLOY T2811
66072	69	ADHESIVE CERMALLOY T2900
66073	69	ADHESIVE CERMALLOY UVC500
66074	69	ADHESIVE CERMALLOY UVI100
66075	72	ADHESIVE CHOBOND 1035
66076	72	ADHESIVE CHOBOND 1038
66077	72	ADHESIVE CHOBOND 360-18
66078	72	ADHESIVE CHOBOND 360-20
66079	73	ADHESIVE CHOBOND 360-208
66080	73	ADHESIVE CHOBOND 4660
66081	73	ADHESIVE CHOBOND 4669
66082	73	ADHESIVE CHOBOND 584-208
66083	73	ADHESIVE CHOBOND 592
66084	39	ADHESIVE ARALDITE RP138
66085	36	ADHESIVE ARALDITE 465A-80-1
66086	36	ADHESIVE ARALDITE 465A-80-2
66087	36	ADHESIVE ARALDITE 506
66088	37	ADHESIVE ARALDITE 507-1
66089	37	ADHESIVE ARALDITE 507-2
66090	37	ADHESIVE ARALDITE 507-3
66091	37	ADHESIVE ARALDITE 507-4
66092	37	ADHESIVE ARALDITE 509
66093	37	ADHESIVE ARALDITE 6004-1
66094	37	ADHESIVE ARALDITE 6004-2
66095	37	ADHESIVE ARALDITE 6020-1
66096	38	ADHESIVE ARALDITE 6020-2
66097	38	ADHESIVE ARALDITE 6020-3
66098	38	ADHESIVE ARALDITE 6060-1
66099	38	ADHESIVE ARALDITE 6060-2
66100	38	ADHESIVE ARALDITE 6060-3
66101	83	ADHESIVE CY8043-1
66102	38	ADHESIVE ARALDITE CY8043-2
66103	38	ADHESIVE ARALDITE DY027-3
66104	39	ADHESIVE ARALDITE GY005-3
66105	39	ADHESIVE ARALDITE GY6005-1
66106	39	ADHESIVE ARALDITE GY6005-2
66107	39	ADHESIVE ARALDITE GY6005-3
66108	39	ADHESIVE ARALDITE GY6005-4
66109	36	ADHESIVE ARALDITE 502
66110	76	ADHESIVE CONBOND 1736 N/F SPRAY
66111	76	ADHESIVE CONBOND 2153
66112	76	ADHESIVE CONBOND 2448
66113	76	ADHESIVE CONBOND 2466
66114	77	ADHESIVE CONBOND 310 WATER BASED CONTACT
66115	77	ADHESIVE CONBOND 360
66116	77	ADHESIVE CONBOND 773
66117	77	ADHESIVE CONBOND 330
66118	76	ADHESIVE CONBOND 272SP
66119	77	ADHESIVE CONBOND 2979
66120	77	ADHESIVE CONBOND 3004
66121	76	ADHESIVE CONBOND 2960
66122	76	ADHESIVE CONBOND
66123	77	ADHESIVE CONBOND 773-40
66124	76	ADHESIVE CONBOND 2620
66125	76	ADHESIVE CONBOND 2214 N/F SUPER SPRAY
66126	76	ADHESIVE CONBOND 2849 N/F SPRAY

MSFC-HDBK-527 REV F 9999942 0006746 3

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
66127	77	ADHESIVE CONBOND 985
66128	180	ADHESIVE KWIKSTIK 1676 N/F
66129	180	ADHESIVE KWIKSTIK 747
66130	180	ADHESIVE KWIKSTIK 516
66131	209	ADHESIVE PANELGRIP 1229
66132	129	ADHESIVE EPO 114 GEL
66133	129	ADHESIVE EPO 114 TI LIQUID
66134	129	ADHESIVE EPO 114 T2 LIQUID
66135	129	ADHESIVE EPO 116 LOW MODULUS
66136	129	ADHESIVE EPO ALL-PURPOSE
66137	192	ADHESIVE MASTIC EPOXY
66138	23	ADHESIVE AD10
66139	24	ADHESIVE AD15
66140	24	ADHESIVE AD16
66141	24	ADHESIVE AD3
66142	24	ADHESIVE AD7
66143	24	ADHESIVE AD8
66144	24	ADHESIVE AD9
66145	74	ADHESIVE CONAP AD1146
66146	74	ADHESIVE CONAP AD1146-1
66147	74	ADHESIVE CONAP AD1146C
66148	74	ADHESIVE CONAP AD1146C1
66149	74	ADHESIVE CONAP AD1147
66150	74	ADHESIVE CONAP AD1147-1
66151	74	ADHESIVE CONAP AD1147C
66152	74	ADHESIVE CONAP AD1147C1
66153	74	ADHESIVE CONAPOXY AD1000
66154	75	ADHESIVE CONAPOXY AD11
66155	75	ADHESIVE CONAPOXY AD12
66156	75	ADHESIVE CONAPOXY AD13
66157	75	ADHESIVE CONAPOXY AD14
66158	75	ADHESIVE CONAPOXY AD17
66159	75	ADHESIVE CONASTIC 830 OIL/GRIP
66160	75	ADHESIVE CONASTIC AD20
66161	75	ADHESIVE CONASTIC G1 SERIES
66162	75	ADHESIVE CONASTIC ST115
66163	105	ADHESIVE EASYPOXY K20
66164	105	ADHESIVE EASYPOXY K22
66165	105	ADHESIVE EASYPOXY K23A
66166	105	ADHESIVE EASYPOXY K256
66167	105	ADHESIVE EASYPOXY K26
66168	105	ADHESIVE EASYPOXY K40
66169	105	ADHESIVE EASYPOXY K45
66170	170	ADHESIVE FR1241/EA055
66171	80	ADHESIVE CREST 1013 A/B
66172	80	ADHESIVE CREST 141 A/B
66173	80	ADHESIVE CREST 170
66174	80	ADHESIVE CREST 173 A/B
66175	80	ADHESIVE CREST 2027 A/B
66176	80	ADHESIVE CREST 2053 A/B
66177	81	ADHESIVE CREST 3170 A/B
66178	81	ADHESIVE CREST 627
66179	80	ADHESIVE CREST 2092 A/B
66180	80	ADHESIVE CREST 2079 A/B
66181	80	ADHESIVE CREST 3119 A/B
66182	80	ADHESIVE CREST 3120 A/B
66183	80	ADHESIVE CREST 3133 A/B
66184	80	ADHESIVE CREST 3135 A/B
66185	81	ADHESIVE CREST 3144 A/B
66186	81	ADHESIVE CREST 3147 A/B
66187		DELETED SEE 66177
66188	81	ADHESIVE CREST 3181
66189	81	ADHESIVE CREST 391 A/B
66190	81	ADHESIVE CREST 642 A/B
66191	81	ADHESIVE CREST 723 A/B
66192	82	ADHESIVE CREST 760 A/B
66193	82	ADHESIVE CREST 800 A/B
66194	82	ADHESIVE CREST 805 A/B
66195	80	ADHESIVE CREST 2154 A/B
66196	81	ADHESIVE CREST 4096 A/B
66197	80	ADHESIVE CREST 2800 A/B
66198		DELETED SEE 65615
66199	259	ADHESIVE THIXON 300/301
66200	259	ADHESIVE THIXON 305
66201	260	ADHESIVE THIXON 409
66202	260	ADHESIVE THIXON 416
66203	260	ADHESIVE THIXON 508
66204	260	ADHESIVE THIXON 511T
66205	260	ADHESIVE THIXON 711
66206	260	ADHESIVE THIXON 752
66207	260	ADHESIVE THIXON 803-1
66208	260	ADHESIVE THIXON 814-1
66209	260	ADHESIVE THIXON 925
66210	260	ADHESIVE THIXON 926
66211	260	ADHESIVE THIXON 927
66212	261	ADHESIVE THIXON 936
66213	261	ADHESIVE THIXON 942
66214	261	ADHESIVE THIXON 943
66215	261	ADHESIVE THIXON 954
66216	261	ADHESIVE THIXON AP3395
66217	261	ADHESIVE THIXON GPO
66218	261	ADHESIVE THIXON OSN2
66219	261	ADHESIVE THIXON P10
66220	261	ADHESIVE THIXON P6-1
66221	261	ADHESIVE THIXON P7
66222	980	PLASTIC M53R/H
66223	87	ADHESIVE DENNISON A30
66224	87	ADHESIVE DENNISON A40
66225	87	ADHESIVE DENNISON A52
66226	88	ADHESIVE DENNISON A53
66227	88	ADHESIVE DENNISON A70
66228	88	ADHESIVE DENNISON A72
66229	88	ADHESIVE DENNISON A73
66230	88	ADHESIVE DENNISON C21
66231	88	ADHESIVE DENNISON C37
66232	88	ADHESIVE DENNISON M11
66233	88	ADHESIVE DENNISON M12
66234	88	ADHESIVE DENNISON M58
66235	88	ADHESIVE DENNISON M9
66236	89	ADHESIVE DEVCON 5-MINUTE EPOXY

MSFC-HDBK-527 REV F ■ 9999942 0006747 5 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
66237	89	ADHESIVE DEVCON 5-MINUTE EPOXY GEL
66238	89	ADHESIVE DEVCON ALUMINUM LIQUID 10710
66239	90	ADHESIVE DEVCON ALUMINUM VERY LIQUID 11720
66240	90	ADHESIVE DEVCON BACKING COMPOUND LIQUID 11915
66241	90	ADHESIVE DEVCON BRONZE PUTTY 10260
66242	90	ADHESIVE DEVCON BRUSHABLE CERAMIC COMPOUND 11760
66243	90	ADHESIVE DEVCON CARBIDE PUTTY 10050
66244	90	ADHESIVE DEVCON CERAMIC WEAR COMPOUND 11680
66245	91	ADHESIVE DEVCON RUBBER 14900
66246	90	ADHESIVE DEVCON EK1
66248	90	ADHESIVE DEVCON EPOXY SEALER 100
66249	90	ADHESIVE DEVCON FLOOR GRIP 13090
66250	90	ADHESIVE DEVCON FLOOR PATCH 13100
66251	90	ADHESIVE DEVCON H-TEMP CERAMIC PUTTY 11690
66252	90	ADHESIVE DEVCON HI-TEMP MOLD MAKER 10370
66253	91	ADHESIVE DEVCON MVP TYPE II
66254	91	ADHESIVE DEVCON PLASTIC/STEEL 5-MINUTE PUTTY
66255	91	ADHESIVE DEVCON PLASTIC/STEEL LIQUID 10210
66256	91	ADHESIVE DEVCON PLASTIC/STEEL PUTTY 10110
66257	91	ADHESIVE DEVCON PUMP REPAIR PUTTY 11700
66258	250	ADHESIVE SILITE RTV HI-TEMP SILICONE
66259	250	ADHESIVE SILITE RTV SILICONE
66260	91	ADHESIVE DEVCON SPECIAL F EPOXY
66261	91	ADHESIVE DEVCON STAINLESS STEEL PUTTY 10270
66262	91	ADHESIVE DEVCON SUPER LOCK-NUT LOCKING GRADE 18520
66263	91	ADHESIVE DEVCON SUPER LOCK-RETAINING GRADE 18540
66264	426	DEVCON SUPER LOCK-SCREW LOCKING GRADE 18510
66265	90	ADHESIVE DEVCON LOCK-STUD LOCKING GRADE 19530
66266	91	ADHESIVE DEVCON LOCK-THREAD LOCKING PENETRANT-SUPER 18560
66267	256	ADHESIVE TANKITE 2
66268	91	ADHESIVE DEVCON TILE ADHESIVE
66269	92	ADHESIVE DEVCON TITANIUM PUTTY
66270	92	ADHESIVE DEVCON WET SURFACE REPAIR PUTTY 11800
66271	279	ADHESIVE ZIPGRIP 100
66272	279	ADHESIVE ZIPGRIP 1500
66273	279	ADHESIVE ZIPGRIP 5
66274	279	ADHESIVE ZIPGRIP 50
66275	279	ADHESIVE ZIPGRIP SUPER GLUE
66276	108	ADHESIVE ECCOBOND 144B
66277	108	ADHESIVE ECCOBOND 1760
66278	108	ADHESIVE ECCOBOND 1765
66279	109	ADHESIVE ECCOBOND 26
66280	109	ADHESIVE ECCOBOND 27
66281	109	ADHESIVE ECCOBOND 276
66282	109	ADHESIVE ECCOBOND 281
66283	109	ADHESIVE ECCOBOND 285-1
66284	109	ADHESIVE ECCOBOND 285-2
66285	109	ADHESIVE ECCOBOND 285-3
66286	110	ADHESIVE ECCOBOND 3-2-5C
66287	110	ADHESIVE ECCOBOND 45
66288	110	ADHESIVE ECCOBOND 45LV
66289	110	ADHESIVE ECCOBOND 51
66290	111	ADHESIVE ECCOBOND 64C
66291	112	ADHESIVE ECCOBOND 64C1
66292		DELETED SEE 65512
66293		DELETED SEE 65512
66294		DELETED SEE 65512
66295	112	ADHESIVE ECCOBOND 87H(NF)
66296	112	ADHESIVE ECCOBOND 91/C11
66297	112	ADHESIVE ECCOBOND 91/C23LV
66298	112	ADHESIVE ECCOBOND 91/C9
66299	111	ADHESIVE ECCOBOND 60C
66300	112	ADHESIVE ECCOBOND SF40
66301	115	ADHESIVE ECCOSORB MF-S
66302	274	ADHESIVE UV153
66303	274	ADHESIVE UV210
66304	274	ADHESIVE UV300
66305	274	ADHESIVE UV307
66306	274	ADHESIVE UV448
66307	274	ADHESIVE UV450
66308	274	ADHESIVE UV900
66309	275	ADHESIVE UV906
66310	275	ADHESIVE UV913
66311	4	ADHESIVE 1 EC1500
66312	4	ADHESIVE 1 EC2500
66313	4	ADHESIVE 1 EC5
66314	4	ADHESIVE 1 EC50
66315	4	ADHESIVE 1 EC90
66316	4	ADHESIVE 1 MC100
66317	4	ADHESIVE 1 MC150
66318	4	ADHESIVE 1 MC50
66319	6	ADHESIVE 2 C100
66320	6	ADHESIVE 2 C50
66321	6	ADHESIVE 2 C500
66322	7	ADHESIVE 3 CI100
66323	7	ADHESIVE 3 CI1000
66324	7	ADHESIVE 3 ST1000
66325	7	ADHESIVE 3 ST5
66326	100	ADHESIVE EA901/A1
66327	100	ADHESIVE EA901/L3
66328	100	ADHESIVE EA911F
66329	101	ADHESIVE EA919/L3
66330	101	ADHESIVE EA929
66331	101	ADHESIVE EA9306
66332	102	ADHESIVE EA9309-2
66333	102	ADHESIVE EA9309-3NA
66334	102	ADHESIVE EA9323
66335	103	ADHESIVE EA9351
66336	104	ADHESIVE EA960F
66337	104	ADHESIVE EA960
66338	152	ADHESIVE EPOXY PATCH KIT 1105
66339	152	ADHESIVE EPOXY PATCH KIT 309
66340	153	ADHESIVE EPOXY PATCH KIT 3X
66341	153	ADHESIVE EPOXY PATCH KIT 615
66342	153	ADHESIVE EPOXY PATCH KIT 6C
66343	100	ADHESIVE EA901NA/L3
66344	104	ADHESIVE EA946/L3-2
66345		DELETED SEE 61447
66346	105	ADHESIVE EA9814NA

MSFC-HDBK-527 REV F 9999942 0006748 7

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
66347	179	ADHESIVE KO1002
66348	179	ADHESIVE KO109
66349	179	ADHESIVE KE4238
66350	179	ADHESIVE KE4239
66351	179	ADHESIVE KO308
66352	179	ADHESIVE KO309
66353		DELETED SEE 66347
66354	180	ADHESIVE KS14
66355	179	ADHESIVE KS0001
66356	180	ADHESIVE KS0002
66357	180	ADHESIVE KS0003
66358	180	ADHESIVE KS4007
66359	180	ADHESIVE KS4008
66360	258	ADHESIVE THERMOFOAM 3028
66361	258	ADHESIVE THERMOFOAM 3050
66362	258	ADHESIVE THERMOFOAM 3056
66363	278	ADHESIVE XEA9369
66364	79	ADHESIVE CONTACT 1001
66365	12	ADHESIVE A R A
66366	188	ADHESIVE M P A MARK II 1087
66367	188	ADHESIVE M P A MARK II 1095
66368	117	ADHESIVE EMPLAST 560
66369	117	ADHESIVE EMBOND 747
66370	188	ADHESIVE M P A MARK II
66371	189	ADHESIVE M90
66372	98	ADHESIVE E41
66373	98	ADHESIVE E39
66374	94	ADHESIVE DOLPHON CA1069
66375	427	DOLPHON CB-1109
66376	94	ADHESIVE DOLPHON CC1024A WITH RE2005
66377	94	ADHESIVE DOLPHON CC1024A WITH RE2000
66378	94	ADHESIVE DOLPHON CC1080
66379	94	ADHESIVE DOLPHON CC1080L
66380	94	ADHESIVE DOLPHON CC1096
66381	94	ADHESIVE DOLPHON CC1099
66382	94	ADHESIVE DOLPHON CC1105
66383	95	ADHESIVE DOLPHON CC1126
66384	95	ADHESIVE DOLPHON CC1129
66385	95	ADHESIVE DOLPHON CR1056-1
66386	95	ADHESIVE DOLPHON CR1056-2
66387	427	DOLCHEM 6009
66388	92	ADHESIVE DOLCHEM 6010
66389	92	ADHESIVE DOLCHEM 6021
66390	92	ADHESIVE DOLCHEM 6029
66391	92	ADHESIVE DOLCHEM 6034
66392	93	ADHESIVE DOLCHEM 6067
66393	93	ADHESIVE DOLCHEM 6070
66394	92	ADHESIVE DOLCHEM 5072
66395	93	ADHESIVE DOLCHEM 6080
66396	93	ADHESIVE DOLCHEM 6100
66397	93	ADHESIVE DOLCHEM 6101
66398	93	ADHESIVE DOLCHEM 6110
66399	93	ADHESIVE DOLCHEM 6111
66400	93	ADHESIVE DOLCHEM 6115
66401	93	ADHESIVE DOLCHEM 6116
66402	93	ADHESIVE DOLCHEM 6121
66403	93	ADHESIVE DOLCHEM 6126
66404	94	ADHESIVE DOLCHEM 6203
66405	94	ADHESIVE DOLCHEM 6210
66406	94	ADHESIVE DOLCHEM 6310/6311
66407	94	ADHESIVE DOLCHEM 6420
66408	94	ADHESIVE DOLCHEM 6488
66409	94	ADHESIVE DOLCHEM 6529
66410	232	ADHESIVE RUBBER SILICONE RTV 92-076
66411	232	ADHESIVE RUBBER SILICONE DC280A
66412	96	ADHESIVE DUHESIVE SPRAY
66413	225	ADHESIVE PYRALUX WA/A
66414	257	ADHESIVE TERATHANE POLYETHER GLOCOLS
66415	276	ADHESIVE VOLAN 9720PP
66416	280	ADHESIVE ZIRCORE FOUNDRY SAND
66417	82	ADHESIVE CUPRINOL OUTDOOR CAULK
66418	220	ADHESIVE POLYSEAMSEAL ALL PURPOSE CAULK
66419	220	ADHESIVE POLYSEAMSEAL 2002 CLEAR CAULK
66420	12	ADHESIVE A3
66421	12	ADHESIVE A33
66422	13	ADHESIVE A40
66423	13	ADHESIVE A41
66424	12	ADHESIVE A110
66425	950	PLASTIC KODAR COPOLYSTER A150 ADHESIVE
66426	12	ADHESIVE A298
66427	13	ADHESIVE A383
66428	13	ADHESIVE A43
66429	13	ADHESIVE A435
66430	13	ADHESIVE A475
66431	13	ADHESIVE A525
66432	13	ADHESIVE A527
66433	14	ADHESIVE A604
66434	14	ADHESIVE A605
66435	14	ADHESIVE A620
66436	14	ADHESIVE A8
66437	12	ADHESIVE A32
66438	13	ADHESIVE A39
66439	12	ADHESIVE A167
66440	13	ADHESIVE A337
66441	13	ADHESIVE A381
66442	189	ADHESIVE M500
66443	189	ADHESIVE M336
66444	171	ADHESIVE G92
66445	12	ADHESIVE A148
66446	13	ADHESIVE A517
66447	13	ADHESIVE A528
66448	14	ADHESIVE A596
66449	14	ADHESIVE A621
66450	14	ADHESIVE A630
66451	86	ADHESIVE DELTABOND 152 WITH C4
66452	87	ADHESIVE DELTABOND 152 WITH D4
66453	87	ADHESIVE DELTACAST 153 WITH A4
66454	87	ADHESIVE DELTACAST 153 WITH B4
66455	87	ADHESIVE DELTACAST 153 WITH C4
66456	87	ADHESIVE DELTACAST 153 WITH D4

MSFC-HDBK-527 REV F 9999942 0006749 9

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
66457	87	ADHESIVE DELTABOND 154 WITH A4
66458	87	ADHESIVE DELTABOND 154 WITH B4
66459	87	ADHESIVE DELTABOND 154 WITH C4
66460	87	ADHESIVE DELTABOND 154 WITH D4
66461	87	ADHESIVE DELTABOND 155
66462	86	ADHESIVE DELTABOND 152 WITH A4
66463	174	ADHESIVE GRILTEX 1G
66464	174	ADHESIVE GRILTEX 2G
66465	174	ADHESIVE GRILTEX 4G
66466	174	ADHESIVE GRILTEX 5G
66467	174	ADHESIVE GRILTEX 6G
66468	174	ADHESIVE GRILTEX 8G
66469	143	ADHESIVE EPOTEK
66470	143	ADHESIVE EPOTEK 301-2
66471	143	ADHESIVE EPOTEK 302
66472	143	ADHESIVE EPOTEK 310
66473	143	ADHESIVE EPOTEK 330
66474	143	ADHESIVE EPOTEK 331
66475	144	ADHESIVE EPOTEK 353ND
66476	144	ADHESIVE EPOTEK 360
66477	144	ADHESIVE EPOTEK 360ST
66478	144	ADHESIVE EPOTEK 360T
66479	144	ADHESIVE EPOTEK 390
66480	144	ADHESIVE EPOTEK 394
66481	144	ADHESIVE EPOTEK 410E
66482	144	ADHESIVE EPOTEK 905
66483	145	ADHESIVE EPOTEK H205
66484	145	ADHESIVE EPOTEK H20E175
66485	145	ADHESIVE EPOTEK H20S
66486	145	ADHESIVE EPOTEK H21D
66487	145	ADHESIVE EPOTEK H22
66488	145	ADHESIVE EPOTEK H27D
66489	145	ADHESIVE EPOTEK H31
66490	145	ADHESIVE EPOTEK H31D
66491	146	ADHESIVE EPOTEK H40
66492	146	ADHESIVE EPOTEK H41
66493	146	ADHESIVE EPOTEK H43
66494	144	ADHESIVE EPOTEK 444
66495	144	ADHESIVE EPOTEK 454
66496	146	ADHESIVE EPOTEK H55
66497	146	ADHESIVE EPOTEK H62
66498	146	ADHESIVE EPOTEK H70E4
66499	146	ADHESIVE EPOTEK H70S
66500	147	ADHESIVE EPOTEK H74
66501	147	ADHESIVE EPOTEK H81
66502	147	ADHESIVE EPOTEK H81E
66503	147	ADHESIVE EPOTEK P10
66504	147	ADHESIVE EPOTEK P1011
66505	155	ADHESIVE EPOXYLITE 211/C383
66506	156	ADHESIVE EPOXYLITE 3101
66507	155	ADHESIVE EPOXYLITE 1462
66508	155	ADHESIVE EPOXYLITE 223
66509	156	ADHESIVE EPOXYLITE 3351
66510	156	ADHESIVE EPOXYLITE 5302
66511	156	ADHESIVE EPOXYLITE 5526
66512	156	ADHESIVE EPOXYLITE 810
66513	157	ADHESIVE EPOXYLITE 8164
66514	157	ADHESIVE EPOXYLITE 8611
66515	157	ADHESIVE EPOXYLITE 8705
66516	157	ADHESIVE EPOXYLITE 8743
66517	157	ADHESIVE EPOXYLITE 8899
66518	157	ADHESIVE EPOXYLITE 8993
66519	50	ADHESIVE BETAMATE 57.541/57.542 STRUCTURAL
66520	50	ADHESIVE BETAMATE 57.511/57.512 STRUCTURAL
66521	99	ADHESIVE E767
66522	232	ADHESIVE S860
66523	160	ADHESIVE F502
66524	208	ADHESIVE P602
66525	208	ADHESIVE P650
66526	208	ADHESIVE P670I
66527	208	ADHESIVE P680
66528	98	ADHESIVE E705
66529	98	ADHESIVE E710
66530	99	ADHESIVE E746
66531	99	ADHESIVE E760
66532	158	ADHESIVE EUCO 456 MORTAR
66533	159	ADHESIVE EUCO 620 GEL
66534	159	ADHESIVE EUCO 620LV
66535	159	ADHESIVE EUCO 620MV
66536	158	ADHESIVE EUCO 352 GEL
66537	158	ADHESIVE EUCO 352LV
66538	158	ADHESIVE EUCO 352MV
66539	158	ADHESIVE EUCO 452 GEL
66540	158	ADHESIVE EUCO 452LV
66541	158	ADHESIVE EUCO 452MV
66542	158	ADHESIVE EUCO 456S
66543	159	ADHESIVE EUCO 460 GEL
66544	159	ADHESIVE EUCO 460LV
66545	159	ADHESIVE EUCO 460MV
66546	159	ADHESIVE EUCO M235 C1
66547	159	ADHESIVE EUCO M235 C2
66548	159	ADHESIVE EUCOPOXY LT
66549	159	ADHESIVE EUCO 520 GEL
66550	159	ADHESIVE EUCO 520MV
66551	159	ADHESIVE EUCO 520LV
66552	160	ADHESIVE FAIRPRENE V2-5159
66553	266	ADHESIVE TRUCAST 111M
66554	83	ADHESIVE CYCLEWELD 5420A/640A
66555	83	ADHESIVE CYCLEWELD C14
66556	163	ADHESIVE FIBER RESIN 7015-1 A/B
66557	163	ADHESIVE FIBER RESIN 7016
66558	163	ADHESIVE FIBER RESIN 7018 A/B
66559	163	ADHESIVE FIBER RESIN 7026
66560	163	ADHESIVE FIBER RESIN 7030
66561	164	ADHESIVE FIBER RESIN 7179
66562	164	ADHESIVE FIBER RESIN 7182
66563	164	ADHESIVE FIBER RESIN 8516
66564	162	ADHESIVE FIBER RESIN 12/HARDENER 5
66565	162	ADHESIVE FIBER RESIN 12/HARDENER 6
66566	162	ADHESIVE FIBER RESIN 13

MSFC-HDBK-527 REV F 9999942 0006750 5

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
66567	162	ADHESIVE FIBER RESIN 3118 A/B
66568	163	ADHESIVE FIBER RESIN 337 POLYURETHANE
66569	163	ADHESIVE FIBER RESIN 5366 POLYURETHANE
66570	163	ADHESIVE FIBER RESIN 7011 POLYURETHANE
66571	163	ADHESIVE FIBER RESIN 7026 POLYURETHANE
66572	163	ADHESIVE FIBER RESIN 7031 POLYURETHANE
66573	163	ADHESIVE FIBER RESIN 7035 POLYURETHANE
66574	163	ADHESIVE FIBER RESIN 7037 POLYURETHANE
66575	163	ADHESIVE FIBER RESIN 7106 POLYURETHANE
66576	164	ADHESIVE FIBER RESIN 7136-2 POLYURETHANE
66577	164	ADHESIVE FIBER RESIN 7162 POLYURETHANE
66578	164	ADHESIVE FIBER RESIN 7171 POLYURETHANE
66579	164	ADHESIVE FIBER RESIN 7176 POLYURETHANE
66580	164	ADHESIVE FIBER RESIN 7183 A/B POLYURETHANE
66581	164	ADHESIVE FIBER RESIN 7332 POLYURETHANE
66582	164	ADHESIVE FIBER RESIN 8193 A/B POLYURETHANE
66583	164	ADHESIVE FIBER RESIN 8194 A/B POLYURETHANE
66584	164	ADHESIVE FIBER RESIN 8503 POLYURETHANE
66585	164	ADHESIVE FIBER RESIN 7336 POLYURETHANE
66586	83	ADHESIVE CYCLEWELD K114 A/B
66587	83	ADHESIVE CYCLEWELD
66588	11	ADHESIVE 80
66589	11	ADHESIVE 85
66590	25	ADHESIVE AF1120
66591	35	ADHESIVE AR1004
66592	35	ADHESIVE AR1100
66593	35	ADHESIVE AR1130
66594	35	ADHESIVE AR1218
66595	35	ADHESIVE AR1418
66596	36	ADHESIVE AR1650
66597	36	ADHESIVE AR1700
66598	116	ADHESIVE ECR4700
66599	116	ADHESIVE ECR4100
66600	116	ADHESIVE ECR4200
66601	116	ADHESIVE ECR4300
66602	256	ADHESIVE TCR2773
66603	256	ADHESIVE TCR12-100
66604	256	ADHESIVE TCR12-15
66605	256	ADHESIVE TCR2820
66606	15	ADHESIVE AB
66607	48	ADHESIVE AS
66608	49	ADHESIVE ASSEMBLY GLUE 160
66609	49	ADHESIVE ASSEMBLY GLUE 65
66610	49	ADHESIVE ASSEMBLY GLUE 70A
66611	49	ADHESIVE ASSEMBLY GLUE 8
66612	49	ADHESIVE ASSEMBLY GLUE 8 PLUS 5%
66613	49	ADHESIVE ASSEMBLY GLUE HIGH TACK
66614	49	ADHESIVE ASSEMBLY GLUE T2A
66615	49	ADHESIVE ASSEMBLY GLUE TX BROWN
66616	181	ADHESIVE LAMINATING 25
66617	181	ADHESIVE LAMINATING GLUE 6W
66618	202	ADHESIVE MULTIBOND AP1 WITH CAT A
66619	202	ADHESIVE MULTIBOND B
66620	203	ADHESIVE MULTIBOND C
66621	203	ADHESIVE MULTIBOND F
66622	203	ADHESIVE MULTIBOND LT1
66623	203	ADHESIVE MULTIBOND LT1 WITH CATALYST W
66624	203	ADHESIVE MULTIBOND RX
66625	203	ADHESIVE MULTIBOND W WITH CATALYST A
66626	203	ADHESIVE MULTIBOND W WITH CATALYST W
66627	262	ADHESIVE TITEBOND 35
66628	262	ADHESIVE TITEBOND 50
66629	262	ADHESIVE TITEBOND 55T
66630	262	ADHESIVE TITEBOND DOWEL DRIVER
66631	262	ADHESIVE TITEBOND IMPERIAL
66632	262	ADHESIVE TITEBOND REGULAR
66633	262	ADHESIVE TITEBOND SUPREME
66634	262	ADHESIVE TOPSPEED ASSEMBLY GLUE
66635	278	ADHESIVE WILLBOND 10
66636	278	ADHESIVE WOODBOND 285
66637	123	ADHESIVE EPIBOND 104 A/B
66638	124	ADHESIVE EPIBOND 1210A/9861
66639	124	ADHESIVE EPIBOND 1217 A/B
66640	124	ADHESIVE EPIBOND 1218 A/B
66641	125	ADHESIVE EPIBOND 126 A/B
66642	125	ADHESIVE EPIBOND 1337/9514A
66643	125	ADHESIVE EPIBOND 1337/9615A
66644	125	ADHESIVE EPIBOND 153 A/B
66645	125	ADHESIVE EPIBOND 1534 A/B
66646	125	ADHESIVE EPIBOND 1543 A/B
66647	126	ADHESIVE EPIBOND 156 A/B
66648	126	ADHESIVE EPIBOND 7000 A/B
66649	126	ADHESIVE EPIBOND 7001 A/B
66650	126	ADHESIVE EPIBOND 7002
66651	126	ADHESIVE EPIBOND 7004
66652	126	ADHESIVE EPIBOND 7100 A/B
66653	126	ADHESIVE EPIBOND 7102
66654	126	ADHESIVE EPIBOND 7103
66655	126	ADHESIVE EPIBOND 7200
66656	806	PLASTIC 610/680
66657	126	ADHESIVE EPIBOND 7202
66658	127	ADHESIVE EPIBOND 7300
66659	127	ADHESIVE EPIBOND 7301
66660	127	ADHESIVE EPIBOND 7375
66661	127	ADHESIVE EPIBOND 8543 A/B
66662	127	ADHESIVE EPIBOND 87680
66663	127	ADHESIVE EPIBOND 87803
66664	127	ADHESIVE EPIBOND 88434
66665	130	ADHESIVE EPOCAST 290 T2
66666		DELETED SEE 06273
66667	273	ADHESIVE URALANE 5754 A/B
66668	273	ADHESIVE URALANE 5759 A/B
66669	273	ADHESIVE URALANE 5764 A/B
66670	131	ADHESIVE EPOCAST 88757
66671	130	ADHESIVE EPOCAST 50-3
66672	130	ADHESIVE EPOCAST 50-2
66673	130	ADHESIVE EPOCAST 50-1
66674	130	ADHESIVE EPOCAST 45
66675	130	ADHESIVE EPOCAST 35
66676	273	ADHESIVE URALANE 88804

MSFC-HDBK-527 REV F 9999942 0006751 7

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
66677	273	ADHESIVE URALANE 88800
66678	273	ADHESIVE URALANE 8089
66679	273	ADHESIVE URALANE 5768
66680	273	ADHESIVE URALANE 5767
66681		DELETED SEE 66669
66683	127	ADHESIVE EPIBOND 88807
66684		DELETED SEE 66644
66685		DELETED SEE 66641
66686	124	ADHESIVE EPIBOND 1210A/9610
66687	124	ADHESIVE EPIBOND 1210A/9615-62
66688		DELETED SEE 66664
66689		DELETED SEE 66663
66690	126	ADHESIVE EPIBOND 1548
66691	126	ADHESIVE EPIBOND 1547
66692	126	ADHESIVE EPIBOND 1546
66693	125	ADHESIVE EPIBOND 1545
66694	125	ADHESIVE EPIBOND 1544
66696	125	ADHESIVE EPIBOND 1539
66697		DELETED SEE 66645
66698	125	ADHESIVE EPIBOND 1526
66699	125	ADHESIVE EPIBOND 1337
66700		DELETED SEE 66640
66701		DELETED SEE 66639
66702		DELETED SEE 66647
66703	124	ADHESIVE EPIBOND 1210A/9615-10
66704		DELETED SEE 66678
66705	170	ADHESIVE G10
66706	171	ADHESIVE GACO AL45
66707	171	ADHESIVE GACO CE2
66708	175	ADHESIVE HP12
66709	204	ADHESIVE N6H
66710	204	ADHESIVE N7
66711	177	ADHESIVE IS802
66712	177	ADHESIVE IS803
66713	177	ADHESIVE IS808
66714	231	ADHESIVE RTV 109
66715	231	ADHESIVE RTV 161
66716	231	ADHESIVE RTV 31
66717	248	ADHESIVE SILGRIP PS 6573
66718	806	PLASTIC 610V/901
66719	203	ADHESIVE N-SIL RTV 128
66720	203	ADHESIVE N-SIL RTV 123
66721	203	ADHESIVE N-SIL RTV 122
66722	245	ADHESIVE SHURSTIK 486
66723	34	ADHESIVE AP138 ALL IN ONE
66724	34	ADHESIVE AP139 ALL IN ONE
66725	66	ADHESIVE CB10
66726	82	ADHESIVE CT20
66727	96	ADHESIVE DW24
66728	170	ADHESIVE FS145
66729	189	ADHESIVE MACCO AW40
66730	189	ADHESIVE MACCO BL70
66731	189	ADHESIVE MACCO C5
66732	190	ADHESIVE MACCO CA80
66733	190	ADHESIVE MACCO CA90
66734	190	ADHESIVE MACCO CERAMIC WALL TILE ADHESIVE M111
66735	190	ADHESIVE MACCO LIQUID NAILS LN60
66736	190	ADHESIVE MACCO LIQUID NAILS LN601
66737	190	ADHESIVE MACCO LIQUID NAILS LN602
66738	190	ADHESIVE MACCO LIQUID NAILS LN603
66739	190	ADHESIVE MACCO LUQUID ROOF REPAIR LR808
66740	190	ADHESIVE MACCO LUQUID WEATHER STRIP LN165
66741	190	ADHESIVE MACCO M112
66742	190	ADHESIVE MACCO M220
66743	190	ADHESIVE MACCO M221
66744	190	ADHESIVE MACCO PV20
66745	190	ADHESIVE MACCO RC711
66746	191	ADHESIVE MACCO SB60
66747	191	ADHESIVE MACCO TA605
66748	191	ADHESIVE MACCO WG166
66749	191	ADHESIVE MACCO WOODWORKERS' GLUE
66750	171	ADHESIVE GC131 ADHESIVE PRIMER
66751	171	ADHESIVE GC3001
66752	173	ADHESIVE GC531 MYLAR ADHESIVE (AEROSPACE)
66753	173	ADHESIVE GC656 ADHESIVE GAP FILLING
66754	173	ADHESIVE GC825 FLEXIBLE EPOXY ADHESIVE
66755	12	ADHESIVE A1216B
66756	213	ADHESIVE PL777
66757	98	ADHESIVE E1103
66758	98	ADHESIVE E2001 A/B
66759	98	ADHESIVE E2101 A/B
66760	98	ADHESIVE E2102 A/B
66761	98	ADHESIVE E2103 A/B
66762	116	ADHESIVE EE1102
66763	117	ADHESIVE EL2705
66764	211	ADHESIVE PL601
66765	211	ADHESIVE PL601 N/P FILM
66766	212	ADHESIVE PL603
66767	212	ADHESIVE PL604
66768	212	ADHESIVE PL605
66769	212	ADHESIVE PL606
66770	212	ADHESIVE PL618-1
66771	212	ADHESIVE PL618-2
66772	212	ADHESIVE PL639 N/P FILM
66773	212	ADHESIVE PL651
66774	212	ADHESIVE PL653EX
66775	212	ADHESIVE PL654GD
66776	212	ADHESIVE PL655
66777	212	ADHESIVE PL655 N/P FILM
66778	212	ADHESIVE PL659
66779	212	ADHESIVE PL717
66780	213	ADHESIVE PL741
66781	213	ADHESIVE PL750
66782	213	ADHESIVE PL751
66783	213	ADHESIVE PL760
66784	213	ADHESIVE PL770
66785	213	ADHESIVE PL776
66786	214	ADHESIVE PLIOBOND 1000
66787	214	ADHESIVE PLIOBOND 1001
66788	214	ADHESIVE PLIOBOND 1005

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006752 9

MATCD	PAGE	DESIGNATION
66789	214	ADHESIVE PLIOBOND 1008
66790	214	ADHESIVE PLIOBOND 1012
66791	214	ADHESIVE PLIOBOND 1014-44
66792	214	ADHESIVE PLIOBOND 1016
66793	214	ADHESIVE PLIOBOND 1018
66794	214	ADHESIVE PLIOBOND 1063
66795	214	ADHESIVE PLIOBOND 1177
66796	214	ADHESIVE PLIOBOND 1240
66797	214	ADHESIVE PLIOBOND 20
66798	215	ADHESIVE PLIOBOND 2000
66799	215	ADHESIVE PLIOBOND 2001
66800	215	ADHESIVE PLIOBOND 2003
66801	215	ADHESIVE PLIOBOND 2004
66802	215	ADHESIVE PLIOBOND 2005
66803	215	ADHESIVE PLIOBOND 2007
66804	215	ADHESIVE PLIOBOND 2011
66805	215	ADHESIVE PLIOBOND 2014
66806	215	ADHESIVE PLIOBOND 2015
66807	215	ADHESIVE PLIOBOND 2021
66808	215	ADHESIVE PLIOBOND 2024
66809	216	ADHESIVE PLIOBOND 2030
66810	216	ADHESIVE PLIOBOND 2033
66811		DELETED SEE 66810
66812	216	ADHESIVE PLIOBOND 2221
66813	216	ADHESIVE PLIOBOND 30
66814	216	ADHESIVE PLIOBOND 40
66815	216	ADHESIVE PLIOBOND 4000
66816	216	ADHESIVE PLIOBOND 4007
66817	216	ADHESIVE PLIOBOND 4014
66818	216	ADHESIVE PLIOBOND 4015
66819	216	ADHESIVE PLIOBOND 4222
66820	216	ADHESIVE PLIOBOND 4237
66821	216	ADHESIVE PLIOBOND 4245
66822	216	ADHESIVE PLIOBOND 4254
66823	217	ADHESIVE PLIOBOND 4275
66824	217	ADHESIVE PLIOBOND 4290
66825	217	ADHESIVE PLIOBOND 5000
66826	217	ADHESIVE PLIOBOND 5001
66827	217	ADHESIVE PLIOBOND 5002
66828	217	ADHESIVE PLIOBOND 5013
66829	217	ADHESIVE PLIOBOND 5015
66830	217	ADHESIVE PLIOBOND 5019
66831	217	ADHESIVE PLIOBOND 5037
66832	217	ADHESIVE PLIOBOND 7001
66833	217	ADHESIVE PLIOBOND 7003
66834	217	ADHESIVE PLIOBOND 7005
66835	217	ADHESIVE PLIOBOND 8000
66836	217	ADHESIVE PLIOBOND 8001
66837	218	ADHESIVE PLIOBOND 8003
66838	218	ADHESIVE PLIOBOND 8004
66839	218	ADHESIVE PLIOBOND 8005
66840	218	ADHESIVE PLIOBOND 9002
66841	218	ADHESIVE PLIOBOND 9005
66842	216	ADHESIVE PLIOBOND 30HT
66843	175	ADHESIVE HM0904
66844	175	ADHESIVE HM0964
66845	175	ADHESIVE HM1756
66846	175	ADHESIVE HM1752
66847	175	ADHESIVE HM1357
66848	129	ADHESIVE EPOCAP 13050
66849	129	ADHESIVE EPOCAP 3195 WITH EPOCURE S-L
66850	147	ADHESIVE EPOWELD 13230
66851	147	ADHESIVE EPOWELD 2156 WITH EPOCURE S9
66852	147	ADHESIVE EPOWELD 2156 WITH EPOCURE 110
66853	147	ADHESIVE EPOWELD 2156 WITH EPOCURE 118
66854	147	ADHESIVE EPOWELD 3243 HIGH IMPACT STRENGTH ADHESIVE
66855	148	ADHESIVE EPOWELD 3583 WITH EPOCURE S-L HIGH IMPACT STRENGTH ADHESIVE
66856	148	ADHESIVE EPOWELD 3650 PASTE FORM HIGH STRENGTH ADHESIVE
66857	148	ADHESIVE EPOWELD 7781
66858	148	ADHESIVE EPOWELD 7895 HIGH STRENGTH GENERAL PURPOSE ADHESIVE
66859	148	ADHESIVE EPOWELD 7903
66860	148	ADHESIVE EPOWELD 7982
66861	148	ADHESIVE EPOWELD 8185
66862	148	ADHESIVE EPOWELD 8200 HIGH IMPACT STRENGTH AD IMPACT STRENGTH ADHESIVE
66863	148	ADHESIVE EPOWELD 8269 20 MINUTE SETTING ADHESIVE
66864	148	ADHESIVE EPOWELD 9143A THIXOTROPIC FLEXIBLE ADHESIVE
66865	204	ADHESIVE OMNIFIT 1150
66866	204	ADHESIVE OMNIFIT 1350
66867	205	ADHESIVE OMNIFIT 1550
66868	205	ADHESIVE OMNIFIT 1570
66869	205	ADHESIVE OMNIFIT 1710
66870	205	ADHESIVE OMNIFIT 1730
66871	205	ADHESIVE OMNIFIT 1750
66872	205	ADHESIVE OMNIFIT 1790
66873	205	ADHESIVE OMNIFIT INSTANT GASKET 10
66874	205	ADHESIVE OMNIFIT INSTANT GASKET 20
66875	245	ADHESIVE SICOMET 40
66876	245	ADHESIVE SICOMET 50
66877	245	ADHESIVE SICOMET 5019
66878	245	ADHESIVE SICOMET 5044
66879	245	ADHESIVE SICOMET 65
66880	245	ADHESIVE SICOMET 7000
66881	245	ADHESIVE SICOMET 77
66882	245	ADHESIVE SICOMET 7900
66883	245	ADHESIVE SICOMET 8200
66884	246	ADHESIVE SICOMET 8300
66885	246	ADHESIVE SICOMET 8400
66886	246	ADHESIVE SICOMET 85
66887	246	ADHESIVE SICOMET 8546
66888	246	ADHESIVE SICOMET 99
66889	275	ADHESIVE VERSAMID 125
66890	57	ADHESIVE BRUTEM 506
66891	57	ADHESIVE BRUTEM 33
66892	57	ADHESIVE BRUTEM 17

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006753 0 ■

MATCD	PAGE	DESIGNATION
66893	57	ADHESIVE BRUTEM 78
66894	57	ADHESIVE BRUTEM 14
66895	219	ADHESIVE POLYPLUS 165
66896	58	ADHESIVE BRUTUM 19HF
66897	58	ADHESIVE BRUTUM 19MP
66898	58	ADHESIVE BRUTUM 19
66899	120	ADHESIVE EP3500 A/B
66900	120	ADHESIVE EP3501 A/B
66901	119	ADHESIVE EP3200 A/B
66902	119	ADHESIVE EP3230 A/B
66903	119	ADHESIVE EP3250 A/B
66904	119	ADHESIVE EP3203 A/B
66905	120	ADHESIVE EP3285 A/B
66906	121	ADHESIVE EP3685
66907	117	ADHESIVE EP1350 A/B
66908	117	ADHESIVE EP1500 A/B
66909	120	ADHESIVE EP3351 A/B
66910	120	ADHESIVE EP3641
66911	120	ADHESIVE EP3642
66912	121	ADHESIVE EP3652
66913	119	ADHESIVE EP3280 A/B
66914	121	ADHESIVE EP3680
66915	120	ADHESIVE EP3281 A/B
66916	117	ADHESIVE EP1300 A/B
66917	117	ADHESIVE EP1330 A/B
66918	178	ADHESIVE JOMAR SEAL "GIMME THE GREEN STUFF"
66919	178	ADHESIVE JOMAR SEAL "THE HEAVYWEIGHT"
66920	179	ADHESIVE JOMAR SEAL "TUFFER THAN TUFF"
66921	179	ADHESIVE JOMAR SEAL W.O.G. SEAL
66922	278	ADHESIVE X-PERT PANEL ADHESIVE
66923	180	ADHESIVE L & M CERAMIC FLOOR ADHESIVE 16
66924	182	ADHESIVE LEFKOWELD 157
66925	182	ADHESIVE LEFKOWELD 209
66926	182	ADHESIVE LEFKOWELD 211
66927	182	ADHESIVE LEFKOWELD 218-5
66928	182	ADHESIVE LEFKOWELD 221
66929	89	ADHESIVE DEPEND 330
66930	184	ADHESIVE LOCTITE 262
66931	184	ADHESIVE LOCTITE 277
66932	186	ADHESIVE LOCTITE 609
66933	186	ADHESIVE LOCTITE 620
66934	186	ADHESIVE LOCTITE 680
66935	188	ADHESIVE LOCTITE QUICK-SET ADHESIVE 404
66936	252	ADHESIVE SPEEDBONDER 324
66937	252	ADHESIVE SPEEDBONDER 325
66938	252	ADHESIVE SPEEDBONDER 326
66939	254	ADHESIVE SUPERBONDER 415
66940	254	ADHESIVE SUPERBONDER 414
66941	254	ADHESIVE SUPERBONDER 420
66942	254	ADHESIVE SUPERBONDER 422
66943	254	ADHESIVE SUPERBONDER 430
66944	70	ADHESIVE CHEMLOK 235
66945	70	ADHESIVE CHEMLOK 236A
66946	70	ADHESIVE CHEMLOK 238
66947	70	ADHESIVE CHEMLOK 246
66948	70	ADHESIVE CHEMLOK 252
66949	70	ADHESIVE CHEMLOK 253
66950	70	ADHESIVE CHEMLOK 402
66951	71	ADHESIVE CHEMLOK 810
66952	71	ADHESIVE CHEMLOK BN
66953	170	ADHESIVE FUSOR EPOXY ADHESIVES
66954	266	ADHESIVE TYRITE 7500
66955	266	ADHESIVE TYRITE URETHANE
66956	275	ADHESIVE VERSILOK 201
66957	275	ADHESIVE VERSILOK 202
66958	276	ADHESIVE VERSILOK 204
66959	276	ADHESIVE VERSILOK 506
66960	276	ADHESIVE VERSILOK 510
66961	276	ADHESIVE VERSILOK 513
66962	276	ADHESIVE VERSILOK 516
66963	276	ADHESIVE VERSILOK 521
66964	276	ADHESIVE VERSILOK 551
66965	276	ADHESIVE VERSILOK 560
66966	276	ADHESIVE VERSILOK ACRYLIC
66967	275	ADHESIVE VERSILOK 101
66968	266	ADHESIVE TYRITE 7602
66969	71	ADHESIVE CHEMLOK G
66970	71	ADHESIVE CHEMLOK GM
66971	71	ADHESIVE CHEMLOK M
66972	71	ADHESIVE CHEMLOK P
66973	71	ADHESIVE CHEMLOK FR
66974	71	ADHESIVE CHEMLOK LR
66975	71	ADHESIVE CHEMLOK R
66976	49	ADHESIVE ASSURE ELECTRICAL TYPE RETAINER
66977	49	ADHESIVE ASSURE ELECTRICAL TYPE THREADLOCKER
66978	49	ADHESIVE ASSURE SURFACE CURING THREADLOCKER
66979	176	ADHESIVE HYSOL EE4183
66980	193	ADHESIVE MERECO "GDO"
66981	193	ADHESIVE MERECO 3446
66982	193	ADHESIVE MERECO 3808
66983	194	ADHESIVE MERECO SN631
66984	194	ADHESIVE MERECO SN632
66985	194	ADHESIVE MERECO SN781
66986	194	ADHESIVE MERECO XL225
66987	194	ADHESIVE MERECO XL294
66988	194	ADHESIVE MERECO XL330
66989	194	ADHESIVE MERECO XL354
66990	195	ADHESIVE MERECO XL373
66991	195	ADHESIVE MERECO XL389
66992	195	ADHESIVE MERECO XL389T
66993	195	ADHESIVE MERECO XLM557
66994	195	ADHESIVE MERECO XLN420/CATALYST 16E
66995	195	ADHESIVE MERECO XLN420/CATALYST XL380
66996	195	ADHESIVE MERECO XLN420/CATALYST XLN474
66997	195	ADHESIVE MERECO XLN470
66998	195	ADHESIVE MERECO XLN490
66999	197	ADHESIVE METALINK 361
67000	197	ADHESIVE METAGRIP 321
67001	198	ADHESIVE METREGRIP 302
67002	198	ADHESIVE METREGRIP 303MV

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006754 2

MATCD	PAGE	DESIGNATION
67003	198	ADHESIVE METREGRIP 303VLV
67004	198	ADHESIVE METREGRIP 30LV
67005	199	ADHESIVE METREGRIP 315
67006	199	ADHESIVE METREGRIP 321
67007	199	ADHESIVE METREGRIP 3446
67008	199	ADHESIVE METREGRIP 355
67009	199	ADHESIVE METREGRIP 385-1
67010	199	ADHESIVE METREGRIP 385-2
67011	198	ADHESIVE METREGRIP 312
67012	228	ADHESIVE RAPIDSET 51QST
67013	228	ADHESIVE RAPIDSET 52SST
67014	228	ADHESIVE RAPIDSET 53HRT
67015	278	ADHESIVE XL279
67016	196	ADHESIVE METACAST 5448 WITH 16E
67017	196	ADHESIVE METACAST 5448 WITH 43
67018	196	ADHESIVE METACAST 1201
67019	194	ADHESIVE MERECO XL342
67020	194	ADHESIVE MERECO SCN568
67021	195	ADHESIVE MERECO XLN589
67022	196	ADHESIVE METADUCT 1201 CN611
67023	196	ADHESIVE METADUCT 1202
67024	196	ADHESIVE METADUCT 1204
67025	196	ADHESIVE METADUCT 1206 SG3
67026	196	ADHESIVE METADUCT 1206 SG4
67027	196	ADHESIVE METADUCT 1212
67028	196	ADHESIVE METADUCT 1216 SERIES
67029	196	ADHESIVE METADUCT 1216-1
67030	196	ADHESIVE METADUCT 1216-2
67031	195	ADHESIVE MERECO XLN425
67032	195	ADHESIVE MERECO XLN455
67033	193	ADHESIVE MERECO CN773 WITH 16E
67034	193	ADHESIVE MERECO CN773 WITH 16C
67035	806	PLASTIC 612B/22NF
67036	193	ADHESIVE MERECO CN934
67037	193	ADHESIVE MERECO CN967
67038	196	ADHESIVE METACAST 5448 WITH #10
67039	194	ADHESIVE MERECO METASIL 5008
67040	228	ADHESIVE RAPIDSET SERIES VISCA CYANOACRYLATE ADH
67041	228	ADHESIVE RAPIDSET SERIES 2
67042	228	ADHESIVE RAPIDSET SERIES 3
67043	193	ADHESIVE MERECO 302
67044	197	ADHESIVE METADUCT 1225 SN736
67045	197	ADHESIVE METADUCT 1225 SN742
67046	197	ADHESIVE METADUCT 1225 XL245
67047	197	ADHESIVE METADUCT XL126
67048	194	ADHESIVE MERECO XL295
67049	197	ADHESIVE METADUCT XLN583 MOD 1
67050	196	ADHESIVE METADUCT 1206
67051	199	ADHESIVE METRESET 3661
67052	199	ADHESIVE METRESET 3662
67053	193	ADHESIVE MERECO METASIL 5002
67054	194	ADHESIVE MERECO METASIL 5004
67055	194	ADHESIVE MERECO METASIL RTV 5005
67056	194	ADHESIVE MERECO METASIL XL152
67057	195	ADHESIVE MERECO XLN449
67058	202	ADHESIVE MIRAPOXY MA800
67059	200	ADHESIVE MIRACLE 40 PLUS
67060	200	ADHESIVE MIRACLE ALL PURPOSE CONSTRUCTION ADHESIVE
67061	200	ADHESIVE MIRACLE BLACK MAGIC TYPE "M"
67062	200	ADHESIVE MIRACLE CA25
67063	200	ADHESIVE MIRACLE CEILING TILE ADHESIVE
67064	200	ADHESIVE MIRACLE CONTACT CEMENT
67065	200	ADHESIVE MIRACLE D617
67066	200	ADHESIVE MIRACLE D518
67067	200	ADHESIVE MIRACLE DSA20
67068	200	ADHESIVE MIRACLE DSA40
67069	200	ADHESIVE MIRACLE GAUGED SLATE ADHESIVE
67070	200	ADHESIVE MIRACLE HT4620
67071	201	ADHESIVE MIRACLE L2000N FACING ADHESIVE
67072	201	ADHESIVE MIRACLE L3000 FACING ADHESIVE
67073	201	ADHESIVE MIRACLE LA69
67074	201	ADHESIVE MIRACLE LA76
67075	201	ADHESIVE MIRACLE LATEX CAULK 'N GLUE
67076	201	ADHESIVE MIRACLE MA200
67077	201	ADHESIVE MIRACLE MA222
67078	201	ADHESIVE MIRACLE MA76
67079	201	ADHESIVE MIRACLE MS120
67080	201	ADHESIVE MIRACLE MS130 "SAFE 'N SOUND"
67081	201	ADHESIVE MIRACLE NON-FLAMMABLE CONTACT CEMENT
67082	201	ADHESIVE MIRACLE PANEL FOAM AND CONSTRUCTION ADHESIVE
67083	201	ADHESIVE MIRACLE PF101
67084	201	ADHESIVE MIRACLE PF102
67085	202	ADHESIVE MIRACLE PF88
67086	202	ADHESIVE MIRACLE PF92
67087	202	ADHESIVE MIRACLE PF95
67088	202	ADHESIVE MIRACLE PF97
67089	202	ADHESIVE MIRACLE RESIN NP428
67090	202	ADHESIVE MIRACLE SFA66
67091	202	ADHESIVE MIRACLE WALLBOARD ADHESIVE
67092	128	ADHESIVE EPIPHEN 825B
67093	51	ADHESIVE BONDMASTER 4500+
67094	52	ADHESIVE BONDMASTER M688 CH16
67095	52	ADHESIVE BONDMASTER M620
67096	52	ADHESIVE BONDMASTER M688 CH8
67097	52	ADHESIVE BONDMASTER M666
67098	192	ADHESIVE MELTHENE M5001
67099	192	ADHESIVE MELTHENE M5002
67100	193	ADHESIVE MELTHENE M5004
67101	193	ADHESIVE MELTHENE M5030
67102	193	ADHESIVE MELTHENE M5311
67103	192	ADHESIVE MELTHENE M1310
67104	193	ADHESIVE MELTHENE M5331
67105	193	ADHESIVE MELTHENE M5400
67106	69	ADHESIVE CHEMGRIP 34
67107	276	ADHESIVE VITON PLV2002
67108	11	ADHESIVE 910
67109		DELETED SEE 67108
67110	210	ADHESIVE PERMALOK HH120
67111	211	ADHESIVE PERMALOK HL126

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006755 4

MATCD	PAGE	DESIGNATION
67112	210	ADHESIVE PERMALOK AL138
67113	211	ADHESIVE PERMALOK HM118
67114	211	ADHESIVE PERMALOK HM128
67115	211	ADHESIVE PERMALOK LM113
67116	211	ADHESIVE PERMALOK MM15
67117	209	ADHESIVE PERMABOND 101
67118	209	ADHESIVE PERMABOND 102
67119	209	ADHESIVE PERMABOND 105
67120	209	ADHESIVE PERMABOND 130
67121	209	ADHESIVE PERMABOND 240
67122	210	ADHESIVE PERMABOND 750
67123		DELETED SEE 67108
67124	210	ADHESIVE PERMALOK 5M060
67125	220	ADHESIVE POWERBOND 919
67126	220	ADHESIVE POWERBOND 920
67127	220	ADHESIVE POWERBOND 922
67128	226	ADHESIVE QUICKBOND 513
67129	226	ADHESIVE QUICKBOND 523
67130	226	ADHESIVE QUICKBOND 610
67131	226	ADHESIVE QUICKBOND 612
67132	226	ADHESIVE QUICKBOND 650
67133	231	ADHESIVE RI2
67134	220	ADHESIVE PR1221 CLASS A
67135	221	ADHESIVE PR1321 CLASS A
67136		DELETED SEE 67135
67137	224	ADHESIVE PR380
67138	224	ADHESIVE PR383
67139	224	ADHESIVE PR2701
67140	224	ADHESIVE PR2702
67141	224	ADHESIVE PR2751
67142	224	ADHESIVE PR2752
67143	224	ADHESIVE PR927
67144	224	ADHESIVE PR938
67145	225	ADHESIVE PR957
67146	223	ADHESIVE PR1710
67147	275	ADHESIVE VANCHEM HM50
67148	232	ADHESIVE S1006
67149	232	ADHESIVE S1010
67150	232	ADHESIVE S1125
67151	227	ADHESIVE R81005
67152	227	ADHESIVE R81007
67153	227	ADHESIVE R81012
67154	227	ADHESIVE R81816
67155	227	ADHESIVE R82007
67156	227	ADHESIVE R82016
67157	227	ADHESIVE R84017
67158	227	ADHESIVE R84025
67159	227	ADHESIVE R84048
67160	227	ADHESIVE R84067
67161	227	ADHESIVE R85013
67162	128	ADHESIVE EPIC 701
67163	128	ADHESIVE EPIC 0104
67164	128	ADHESIVE EPIC R1011
67165	128	ADHESIVE EPIC R103D
67166	128	ADHESIVE EPIC R2027
67167	128	ADHESIVE EPIC R3500
67168	128	ADHESIVE EPIC S7002
67169	129	ADHESIVE EPOC RESIN 0108
67170	226	ADHESIVE R1003
67171	226	ADHESIVE R1007
67172	226	ADHESIVE R3500
67173	244	ADHESIVE SHELDAHL AKC012
67174	244	ADHESIVE SHELDAHL MKC021
67175	245	ADHESIVE SHELDAHL T329
67176	244	ADHESIVE SHELDAHL T1694
67177	245	ADHESIVE SHELDAHL T400
67178	244	ADHESIVE SHELDAHL T100
67179	244	ADHESIVE SHELDAHL L1662
67180	244	ADHESIVE SHELDAHL T1633
67181	244	ADHESIVE SHELDAHL T1650
67182	245	ADHESIVE SHELDAHL T340
67183	244	ADHESIVE SHELDAHL T1502
67185	252	ADHESIVE SOLUBOND 1173
67186	252	ADHESIVE SOLUBOND 1177
67187	251	ADHESIVE SOLUBOND 1119
67188	251	ADHESIVE SOLUBOND 1122
67189	251	ADHESIVE SOLUBOND 1168
67190	256	ADHESIVE T440
67191	256	ADHESIVE T165
67192	203	ADHESIVE N134
67193	170	ADHESIVE G404
67194	58	ADHESIVE C111
67195	267	ADHESIVE U148
67196	255	ADHESIVE SWS990
67197	255	ADHESIVE SWS931
67198	255	ADHESIVE SWST60
67199	74	ADHESIVE CON/RTV-SC
67200	206	ADHESIVE P/N 72-00008
67201	74	ADHESIVE CON/RTV-I
67202	74	ADHESIVE CON/RTV-II
67203	74	ADHESIVE CON/RTV-NI
67204	209	ADHESIVE PARALAC DPB278
67205	209	ADHESIVE PARALAC RC57
67206	257	ADHESIVE THERMALBOND
67207	4	ADHESIVE 1099L
67208	5	ADHESIVE 1300 ROLL COATABLE
67209	5	ADHESIVE 1751 B/A
67210	5	ADHESIVE 1838 B/A TAN
67211	5	ADHESIVE 1838L B/A TRANSLUCENT
67212	5	ADHESIVE 1870
67213	6	ADHESIVE 2141
67214	6	ADHESIVE 2216 B/A FAST CURE TRANSLUCENT
67215	160	ADHESIVE FASTBOND 30NF GREEN
67216	160	ADHESIVE FASTBOND 30NF NEUTRAL
67217	7	ADHESIVE 33 RED
67218	7	ADHESIVE 34 NEUTRAL
67219	160	ADHESIVE FASTBOND 35NF BLUE
67220	7	ADHESIVE 3501 B/A CLEAR
67221	7	ADHESIVE 3533 B/A CLEAR
67222	7	ADHESIVE 3533 B/A GREY

MSFC-HDBK-527 REV F 9999942 0006756 6

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
67223	8	ADHESIVE 3570 B/A CLEAR
67224	8	ADHESIVE 36 BLACK
67225	8	ADHESIVE 37 BLACK SELF EXTINGUISHING
67226	160	ADHESIVE FASTBOND 38NF BLACK SELF-EXTINGUISHING
67227	8	ADHESIVE 3M AEROSOL 90
67228	9	ADHESIVE 3M AEROSOL SUPER 77N
67229	161	ADHESIVE FASTBOND 42NF
67230	161	ADHESIVE FASTBOND 42NF PLUS
67231	160	ADHESIVE FASTBOND 4213NF
67232	160	ADHESIVE FASTBOND 4268NF
67233	161	ADHESIVE FASTBOND 4289NF
67234	161	ADHESIVE FASTBOND 45NF CLEAR
67235	161	ADHESIVE FASTBOND 45NF ORANGE
67236	9	ADHESIVE 4550
67237	161	ADHESIVE FASTBOND 47NF CLEAR
67238	9	ADHESIVE 4799
67239	161	ADHESIVE FASTBOND 4910NF
67240	806	PLASTIC 616N/901
67241	9	ADHESIVE 5 GREEN
67242	9	ADHESIVE 5 NEUTRAL
67243	806	PLASTIC 616N/681
67244	806	PLASTIC 618/900C
67245	10	ADHESIVE 5230
67246	10	ADHESIVE 75
67247	11	ADHESIVE 826
67248	806	PLASTIC 622/680
67249	11	ADHESIVE 847H
67250	11	ADHESIVE 847L
67251	161	ADHESIVE FASTBOND 871NF
67252	11	ADHESIVE 880
67253	11	ADHESIVE 959
67254	60	ADHESIVE CASE SEALING ADHESIVE EC4365
67255	95	ADHESIVE DP100 CLEAR
67256	95	ADHESIVE DP105 CLEAR
67257	95	ADHESIVE DP110 CLEAR
67258	95	ADHESIVE DP110 GRAY
67259	95	ADHESIVE DP190 GRAY
67260	175	ADHESIVE HIGH STRENGTH ADHESIVE 90
67261	177	ADHESIVE JET MELT 3735
67262	178	ADHESIVE JET MELT 3790
67263	177	ADHESIVE JET MELT 3736
67264	177	ADHESIVE JET MELT 3738
67265	178	ADHESIVE JET MELT 3740
67266	178	ADHESIVE JET MELT 3758
67267	178	ADHESIVE JET MELT 3762
67268	178	ADHESIVE JET MELT 3764
67269	178	ADHESIVE JET MELT 3765
67270	178	ADHESIVE JET MELT 3779
67271	178	ADHESIVE JET MELT 3783
67272	178	ADHESIVE JET MELT 3788
67273	178	ADHESIVE JET MELT 3792
67274	178	ADHESIVE JET MELT 3796
67275	178	ADHESIVE JET MELT 3797
67276	180	ADHESIVE LABELING ADHESIVE EC4944
67277	208	ADHESIVE PALLETING ADHESIVE EC4650
67278	806	PLASTIC 622/GE
67279	806	PLASTIC 638/45
67280		DELETED SEE 60235
67281	807	PLASTIC 655/555
67282	239	ADHESIVE SCOTCHWELD 3532 B/A
67283	239	ADHESIVE SCOTCHWELD 3535 B/A
67284	240	ADHESIVE SCOTCHWELD 776
67285	238	ADHESIVE SCOTCHWELD 1357L
67286	239	ADHESIVE SCOTCHWELD 2262
67287	240	ADHESIVE SCOTCHWELD 4475
67288	240	ADHESIVE SCOTCHWELD 4693
67289	237	ADHESIVE SCOTCHMELT E3861
67290	238	ADHESIVE SCOTCHSEAL 5200
67291	233	ADHESIVE SCOTCHCAST 208
67292	233	ADHESIVE SCOTCHCAST 210
67293	233	ADHESIVE SCOTCHCAST 215
67294	233	ADHESIVE SCOTCHCAST 216
67295	233	ADHESIVE SCOTCHCAST 226
67296	233	ADHESIVE SCOTCHCAST 237
67297	233	ADHESIVE SCOTCHCAST 241
67298	234	ADHESIVE SCOTCHCAST 243
67299	234	ADHESIVE SCOTCHCAST 250
67300	234	ADHESIVE SCOTCHCAST 252
67301	234	ADHESIVE SCOTCHCAST 253
67302	234	ADHESIVE SCOTCHCAST 255
67303	234	ADHESIVE SCOTCHCAST 260
67304	234	ADHESIVE SCOTCHCAST 262
67305	234	ADHESIVE SCOTCHCAST 263
67306	234	ADHESIVE SCOTCHCAST 265
67307	234	ADHESIVE SCOTCHCAST 270
67308	235	ADHESIVE SCOTCHCAST 282
67309	235	ADHESIVE SCOTCHCAST 3
67310	235	ADHESIVE SCOTCHCAST 5064
67311	235	ADHESIVE SCOTCHCAST 5140
67312	235	ADHESIVE SCOTCHCAST 5166
67314	235	ADHESIVE SCOTCHCAST 5235
67315	235	ADHESIVE SCOTCHCAST 5237
67316	235	ADHESIVE SCOTCHCAST 5240
67317	235	ADHESIVE SCOTCHCAST 5241
67318	235	ADHESIVE SCOTCHCAST 5242
67319	235	ADHESIVE SCOTCHCAST 5243
67320	235	ADHESIVE SCOTCHCAST 5326
67321	235	ADHESIVE SCOTCHCAST 9
67322	254	ADHESIVE SUPER 77 SPRAY
67323	807	PLASTIC 676F/86
67324	807	PLASTIC 677F/70
67325	240	ADHESIVE SCOTCHWELD AF163-24
67326	242	ADHESIVE SCOTCHWELD IXA3448
67327	240	ADHESIVE SCOTCHWELD AF163-2K
67328	240	ADHESIVE SCOTCHWELD AF163-2M
67329	240	ADHESIVE SCOTCHWELD AF163-205T
67330	240	ADHESIVE SCOTCHWELD EC1648
67331	240	ADHESIVE SCOTCHWELD EC1614
67332	240	ADHESIVE SCOTCHWELD EC1169
67333	805	PLASTIC 606/21

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006757 8

MATCD	PAGE	DESIGNATION
67334	806	PLASTIC 6164-2/21
67335	807	PLASTIC 7/308R/N
67336	805	PLASTIC 607AA/22NF
67337	805	PLASTIC 608-10/12N
67338	805	PLASTIC 608-10TLS/12NLS
67339	237	ADHESIVE SCOTCHGRIP 4518
67340	807	PLASTIC 670/70
67341	905	PLASTIC F180R/F181H
67342	806	PLASTIC 6410R/H
67343	238	ADHESIVE SCOTCHWELD 1751L
67344	905	PLASTIC F18 R/H
67345	106	ADHESIVE EC1828
67346	106	ADHESIVE EC1386
67347	208	ADHESIVE PA4887
67348	25	ADHESIVE AF126
67349	107	ADHESIVE EC3903
67350	107	ADHESIVE EC3500 B/A
67351	26	ADHESIVE AF3024
67352	25	ADHESIVE AF131
67353	25	ADHESIVE AF30
67354	26	ADHESIVE AF31
67355	107	ADHESIVE EC3569 B/A
67356	9	ADHESIVE 4323
67357	982	PLASTIC MARASET F18
67358	982	PLASTIC MARASET 641D
67359	982	PLASTIC MARASET F180R
67360	982	PLASTIC MARASET 670L
67361	981	PLASTIC MARASET 608-10TLS
67362	981	PLASTIC MARASET 607AA
67363	981	PLASTIC MARASET 606
67364	265	ADHESIVE TRADUCT 2924
67365	265	ADHESIVE TRABOND 2248
67366	265	ADHESIVE TRABOND 2230
67367	265	ADHESIVE TRABOND KSNA
67368	265	ADHESIVE TRABOND 2225
67369	265	ADHESIVE TRABOND 2254
67370	263	ADHESIVE TRABOND 2126
67371	263	ADHESIVE TRABOND 2129
67372	263	ADHESIVE TRABOND 2130
67373	263	ADHESIVE TRABOND 2132
67374	263	ADHESIVE TRABOND 2133
67375	263	ADHESIVE TRABOND 21350
67376	264	ADHESIVE TRABOND 2143D
67377	264	ADHESIVE TRABOND 2147
67378	264	ADHESIVE TRABOND 2151
67379	264	ADHESIVE TRABOND 2161
67380	264	ADHESIVE TRABOND 21620
67381	264	ADHESIVE TRABOND 2165
67382	264	ADHESIVE TRABOND 2190
67383	264	ADHESIVE TRABOND 2202
67384	264	ADHESIVE TRABOND 2203
67385	264	ADHESIVE TRABOND 2208
67386	264	ADHESIVE TRABOND 2211
67387	264	ADHESIVE TRABOND 2212
67388	264	ADHESIVE TRABOND 2215
67389	262	ADHESIVE TRABOND 2101
67390	262	ADHESIVE TRABOND 2106
67391	262	ADHESIVE TRABOND 2106T
67392	262	ADHESIVE TRABOND 2111
67393	263	ADHESIVE TRABOND 2113
67394	263	ADHESIVE TRABOND 2114
67395	263	ADHESIVE TRABOND 2115
67396	263	ADHESIVE TRABOND 2122
67397	263	ADHESIVE TRABOND 2123
67398	263	ADHESIVE TRABOND 2124
67399	263	ADHESIVE TRABOND 2125
67400	148	ADHESIVE EPOXY 10
67401	149	ADHESIVE EPOXY 12
67402	149	ADHESIVE EPOXY 13
67403	149	ADHESIVE EPOXY 14
67404	149	ADHESIVE EPOXY 15
67405	149	ADHESIVE EPOXY 16
67406	149	ADHESIVE EPOXY 17
67407	149	ADHESIVE EPOXY 20
67408	149	ADHESIVE EPOXY 30
67409	149	ADHESIVE EPOXY 50
67410	149	ADHESIVE EPOXY 850
67411	150	ADHESIVE EPOXY BOND ADHESIVE
67412	173	ADHESIVE GE10
67413	173	ADHESIVE GE20
67414	173	ADHESIVE GE30
67415	173	ADHESIVE GE40
67416	199	ADHESIVE MICROCIRCUIT SILVER TYPE K
67417	199	ADHESIVE MICROCIRCUIT SILVER TYPE L
67418	199	ADHESIVE MICROCIRCUIT SILVER TYPE N
67419	199	ADHESIVE MICROCIRCUIT SILVER TYPE O
67420	250	ADHESIVE SILVER BOND TYPE 40
67421	250	ADHESIVE SILVER BOND TYPE 50
67422	250	ADHESIVE SILVER BOND TYPE 60
67423	250	ADHESIVE SILVER EPOXY PASTE TYPE 1 AND 2
67424	251	ADHESIVE SMA100
67425	251	ADHESIVE SMA1600
67426	251	ADHESIVE SMA200
67427	251	ADHESIVE SMA300
67428	251	ADHESIVE SMA400
67429	251	ADHESIVE SMA500
67430	251	ADHESIVE SMA600
67431	265	ADHESIVE TRANSEAL 1175T
67432	265	ADHESIVE TRANSENE PDA D500
67433	266	ADHESIVE TRANSENE PDA S500
67434	204	ADHESIVE NICKEL BOND TYPE 40
67435	204	ADHESIVE NICKEL BOND TYPE 50
67436	204	ADHESIVE NICKEL BOND TYPE 60
67437	12	ADHESIVE A PRIMER
67438	31	ADHESIVE AMSCO RES 3001
67439	30	ADHESIVE AMSCO RES 202A
67440	31	ADHESIVE AMSCO RES 3008
67441	31	ADHESIVE AMSCO RES 3001P
67442	31	ADHESIVE AMSCO RES 3034
67443	31	ADHESIVE AMSCO RES 3063

MSFC-HDBK-527 REV F 9999942 0006758 T

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
67444	31	ADHESIVE AMSCO RES 3151
67445	31	ADHESIVE AMSCO RES 4000
67446	31	ADHESIVE AMSCO RES 4040
67447	31	ADHESIVE AMSCO RES 4072
67448	31	ADHESIVE AMSCO RES 4104 (65/35)
67449	32	ADHESIVE AMSCO RES 6130 (HS/SS)
67450	32	ADHESIVE AMSCO RES 528
67451	32	ADHESIVE AMSCO RES 542
67452	32	ADHESIVE AMSCO RES 546
67453	34	ADHESIVE AMSCO RES 930
67454	34	ADHESIVE AMSCO RES 931
67455	34	ADHESIVE AMSCO RES 940
67456	34	ADHESIVE AMSCO RES M3153
67457	33	ADHESIVE AMSCO RES 7200
67458	33	ADHESIVE AMSCO RES 8795
67459	33	ADHESIVE AMSCO RES 9000
67460	33	ADHESIVE AMSCO RES 9001
67461	33	ADHESIVE AMSCO RES 9102
67462	33	ADHESIVE AMSCO RES 9105
67463	33	ADHESIVE AMSCO RES 9201
67464	33	ADHESIVE AMSCO RES 9202
67465	33	ADHESIVE AMSCO RES 9202V60
67466	33	ADHESIVE AMSCO RES 9204
67467	33	ADHESIVE AMSCO RES 9211
67468	33	ADHESIVE AMSCO RES 9213
67469	34	ADHESIVE AMSCO RES 9218
67470	30	ADHESIVE AMSCO RES 19RB64P
67471	32	ADHESIVE AMSCO RES 6206
67472		DELETED SEE 67444
67473	32	ADHESIVE AMSCO RES 6213
67474	30	ADHESIVE AMSCO RES 19BR64
67475	31	ADHESIVE AMSCO RES 3004
67476	982	PLASTIC MARASET M53
67477	30	ADHESIVE AMSCO RES 202AH
67478	30	ADHESIVE AMSCO RES 202AM
67479	31	ADHESIVE AMSCO RES 5007
67480	34	ADHESIVE AMSCO RES S55
67481	982	PLASTIC MARASET 7-308
67482	982	PLASTIC MARASET 6164-2
67483	32	ADHESIVE AMSCO RES 6255
67484	33	ADHESIVE AMSCO RES 9214
67485	34	ADHESIVE AMSCO RES 9621
67486	34	ADHESIVE AMSCO RES 9622
67487	32	ADHESIVE AMSCO RES 6221
67488	33	ADHESIVE AMSCO RES 9205
67489	982	PLASTIC MARASET 677F
67490	982	PLASTIC MARASET 676F
67491	982	PLASTIC MARASET 622
67492	32	ADHESIVE AMSCO RES 6272
67493	982	PLASTIC MARASET 618
67494	982	PLASTIC MARASET 616N
67495	32	ADHESIVE AMSCO RES 6222
67496	32	ADHESIVE AMSCO RES 6247
67497	981	PLASTIC MARASET 13N
67498	32	ADHESIVE AMSCO RES 6038
67499	32	ADHESIVE AMSCO RES 6150 (45/55)
67500	981	PLASTIC MARASET 610
67501	32	ADHESIVE AMSCO RES 6105 (45/55)
67502	31	ADHESIVE AMSCO RES 4000 (50/50)
67503	31	ADHESIVE AMSCO RES 4001
67504	981	PLASTIC MARASET 610V
67505	34	ADHESIVE AMSCO RES P528F
67506	34	ADHESIVE AMSCO RES P546
67507	246	ADHESIVE SILAPRENE ALL WEATHER SEALANT
67508	246	ADHESIVE SILAPRENE ADHESIVE/SEALANT
67509	248	ADHESIVE SILAPRENE MS038
67510	246	ADHESIVE SILAPRENE M6102
67511	246	ADHESIVE SILAPRENE M6128
67512	246	ADHESIVE SILAPRENE M6130
67513	246	ADHESIVE SILAPRENE M6164
67514	247	ADHESIVE SILAPRENE M6234
67515	247	ADHESIVE SILAPRENE M6249
67516	247	ADHESIVE SILAPRENE M6272
67517	247	ADHESIVE SILAPRENE M6287
67518	247	ADHESIVE SILAPRENE M6302
67519	247	ADHESIVE SILAPRENE M6303
67520	247	ADHESIVE SILAPRENE M6306
67521	247	ADHESIVE SILAPRENE M6310
67522	247	ADHESIVE SILAPRENE M6314
67523	247	ADHESIVE SILAPRENE M6321
67524	247	ADHESIVE SILAPRENE M6347
67525	247	ADHESIVE SILAPRENE M6378
67526	247	ADHESIVE SILAPRENE M644D
67527	247	ADHESIVE SILAPRENE M6531
67528	248	ADHESIVE SILAPRENE M6562
67529	248	ADHESIVE SILAPRENE M6571
67530	248	ADHESIVE SILAPRENE M6579
67531	248	ADHESIVE SILAPRENE M6587
67532	82	ADHESIVE CV1142
67533	82	ADHESIVE CV1143
67534	82	ADHESIVE CV12570
67535	83	ADHESIVE CV2564
67536	83	ADHESIVE CV2568
67537	189	ADHESIVE M-BOND GA2
67538	189	ADHESIVE M-BOND GA100
67539	188	ADHESIVE M-BOND 43B
67540	189	ADHESIVE M-BOND GA61
67541	189	ADHESIVE M-BOND AE15
67542	189	ADHESIVE M-BOND A12
67543	176	ADHESIVE HYSOL RE2039
67544	177	ADHESIVE IMPRUV GENERAL PURPOSE ADHESIVE
67545	177	ADHESIVE IMPRUV SEALANT/ADHESIVE
67546	185	ADHESIVE LOCTITE 324
67547	185	ADHESIVE LOCTITE 326
67548		DELETED SEE 63526
67549	188	ADHESIVE LOCTITE ULTRA PERFORMANCE TAX PAK
67550	205	ADHESIVE OUTPUT THERMAL CONDUCTIVE ADHESIVE
67551	206	ADHESIVE OUTPUT THERMAL CONDUCTIVE ADHESIVE REPAIRABLE
67552	254	ADHESIVE SUPERBONDER 498

MSFC-HDBK-527 REV F 9999942 0006759 1

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
67553	261	ADHESIVE THREADLOCKER 222
67554	261	ADHESIVE THREADLOCKER 242
67555	261	ADHESIVE THREADLOCKER 290
67556	228	ADHESIVE RAYBOND R85014
67557	228	ADHESIVE RAYBOND R86009
67558	229	ADHESIVE RAYBOND R86025
67559	52	ADHESIVE BONDMASTER M606
67560	209	ADHESIVE PANEL AND FOAM #104
67561	276	ADHESIVE WALLBOARD ADHESIVE #108
67562	252	ADHESIVE SOUNDSEAL ACOUSTICAL #909
67563	96	ADHESIVE DUR METAL SUPER-RAPID WEAR RESISTANT
67564	277	ADHESIVE WEAR RESISTANT LIQUID #11220
67565	277	ADHESIVE WEAR RESISTANT PUTTY #11420
67566	161	ADHESIVE FASTBOND INSULATION ADHESIVE 33 RED
67567	161	ADHESIVE FASTBOND INSULATION ADHESIVE 34 TRANSLUCENT
67568	161	ADHESIVE FASTBOND INSULATION ADHESIVE 35NF BLUE
67569	161	ADHESIVE FASTBOND INSULATION ADHESIVE 36 BLACK
67570	161	ADHESIVE FASTBOND INSULATION ADHESIVE 37 BLACK
67571	161	ADHESIVE FASTBOND INSULATION ADHESIVE 38NF BLACK
67572		DELETED SEE 67229
67573		DELETED SEE 67230
67574		DELETED SEE 67234
67575		DELETED SEE 67235
67576		DELETED SEE 67237
67577	237	ADHESIVE SCOTCHGRIP 847L
67578	237	ADHESIVE SCOTCHGRIP 847H
67579	237	ADHESIVE SCOTCHGRIP 5034 NEUTRAL
67580	160	ADHESIVE FASTBOND 30 GREEN AND NEUTRAL
67581	242	ADHESIVE SCOTCHWELD FILM AF6
67582	242	ADHESIVE SCOTCHWELD FILM AF10
67583	242	ADHESIVE SCOTCHWELD FILM AF13
67584	242	ADHESIVE SCOTCHWELD FILM AF32
67585	242	ADHESIVE SCOTCHWELD FILM AF111
67586	242	ADHESIVE SCOTCHWELD FILM AF147
67587	242	ADHESIVE SCOTCHWELD FILM AF202
67588	242	ADHESIVE SCOTCHWELD IXA3430
67589	241	ADHESIVE SCOTCHWELD EC3420
67590	241	ADHESIVE SCOTCHWELD EC3446
67591	241	ADHESIVE SCOTCHWELD EC3448
67592	242	ADHESIVE SCOTCHWELD IXA3537
67593	242	ADHESIVE SCOTCHWELD IXA3538
67594	242	ADHESIVE SCOTCHWELD IXA3580
67595	35	ADHESIVE AQUAFORTE 108W
67596	218	ADHESIVE POLAQUA 123-07
67597	218	ADHESIVE POLAQUA 127-07
67598	218	ADHESIVE POLAQUA 103L
67599	183	ADHESIVE LIGHTWELD 401
67600	982	PLASTIC MARASET 612B
67601	183	ADHESIVE LIGHTWELD 458
67602	818	PLASTIC AM400 (PCTFE)
67603	183	ADHESIVE LIGHTWELD 625
67604	820	PLASTIC AP1500 SPRAYABLE PRIMAFILL
67605	183	ADHESIVE LIGHTWELD 911
67606	183	ADHESIVE LIGHTWELD 912
67607	182	ADHESIVE LIGHTWELD 183
67608	183	ADHESIVE LIGHTWELD 184
67609	183	ADHESIVE LIGHTWELD 185
67610	183	ADHESIVE LIGHTWELD 305
67611	97	ADHESIVE DYMAX 901
67612	97	ADHESIVE DYMAX 902
67613	183	ADHESIVE LIGHTWELD 432
67614	14	ADHESIVE AA1104
67615	15	ADHESIVE AA1122
67616	15	ADHESIVE AA1128
67617	15	ADHESIVE AA1130
67618	15	ADHESIVE AA1124
67619	15	ADHESIVE AA1604
67620	14	ADHESIVE AA1106
67621	14	ADHESIVE AA1108
67622	15	ADHESIVE AA1612
67623	15	ADHESIVE AA1212
67624	11	ADHESIVE 80X12
67625	15	ADHESIVE AA1120
67626	15	ADHESIVE AA2304
67627	15	ADHESIVE AA1116
67628	177	ADHESIVE ISOSET WD2A312
67629	177	ADHESIVE ISOSET WD3A320
67630	48	ADHESIVE AROSET 2022W50
67631	48	ADHESIVE AROSET 2201W50
67632	48	ADHESIVE AROSET 2202W50
67633	48	ADHESIVE AROSET 2301W50
67634	48	ADHESIVE AROSET 2302W50
67635	48	ADHESIVE AROSET 2431W50
67636	48	ADHESIVE AROSET 2532W50
67637	75	ADHESIVE CONAPOXY AD1040B/CONACURE EA073A
67638	253	ADHESIVE STONEPOXY KIT #6-2
67639	86	ADHESIVE DC96-081 RTV
67640	86	ADHESIVE DC96-083
67641	50	ADHESIVE BETAMATE 435.71
67642	50	ADHESIVE BETAMATE 435.72
67643	50	ADHESIVE BETAMATE 435.81
67644	192	ADHESIVE MARK 3
67645	191	ADHESIVE MARK 10
67646	191	ADHESIVE MARK 10.3
67647	191	ADHESIVE MARK 19
67648	191	ADHESIVE MARK 24
67649	192	ADHESIVE MARK 25
67650	192	ADHESIVE MARK 25.3
67651	192	ADHESIVE MARK 29
67652	192	ADHESIVE MARK 30
67653	192	ADHESIVE MARK 30.1
67654	132	ADHESIVE EPON 813
67655	134	ADHESIVE EPON 823
67656	132	ADHESIVE EPON 8132
67657	141	ADHESIVE EPON 829
67658	141	ADHESIVE EPON 8294
67659	141	ADHESIVE EPON 830
67660	141	ADHESIVE EPON 8280
67661	131	ADHESIVE EPON 1001F

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006760 8 ■

MATCD	PAGE	DESIGNATION
67662	131	ADHESIVE EPON 1002F
67663	131	ADHESIVE EPON 1004F
67664	131	ADHESIVE EPON 1007F
67665	131	ADHESIVE EPON 1009F
67666	141	ADHESIVE EPON 834
67667	142	ADHESIVE EPON 836
67668	142	ADHESIVE EPON 841
67669	142	ADHESIVE EPON 871
67670	142	ADHESIVE EPON 872
67671	142	ADHESIVE EPON 872X75
67672	131	ADHESIVE EPON 1031
67673	132	ADHESIVE EPON 1031B-80
67674	132	ADHESIVE EPON 1031A-70
67675	142	ADHESIVE EPON DPS164
67676	231	ADHESIVE RTC EPOXY
67677	59	ADHESIVE CA2005L
67678	56	ADHESIVE BR104 EPOXY
67679	175	ADHESIVE HIGH STRENGTH RTC EPOXY
67680	176	ADHESIVE HYSOL EPOXY
67681	57	ADHESIVE BR610
67682	156	ADHESIVE EPOXYLITE 813
67683		DELETED SEE 66512
67684	57	ADHESIVE BR22
67685	213	ADHESIVE PLD700
67686	236	ADHESIVE SCOTCHGRIP 1357 NEUTRAL
67687	820	PLASTIC AP1001-4 FILLER PASTE #4
67688	820	PLASTIC AP1001-7 AKEMI FILLER NO 7
67689	6	ADHESIVE 221H-HI
67690	6	ADHESIVE 2214 HIGH DENSITY
67691	6	ADHESIVE 2214 HIGH FLEX
67692	6	ADHESIVE 2214 NON-METALLIC FIELD
67693	180	ADHESIVE L & M CERAMIC FLOOR ADHESIVE B272
67694	180	ADHESIVE L & M CERAMIC WALL TILE ADHESIVE A282
67695	180	ADHESIVE L & M MULTI-PURPOSE CERAMIC WALL AND TILE ADH TYPE 1 B-289
67696	237	ADHESIVE SCOTCHGRIP 2226 GREEN
67697	160	ADHESIVE FA13
67698	1,188	PLASTIC TP-901 HARDSET TOOLING PASTE
67699	821	PLASTIC AP3030 COLD SOLDER TYPE FILLER PASTE
67700	820	PLASTIC AP2206 SURFACE COAT
67701	820	PLASTIC AP2209 EPOXY SURFACE COAT
67702	820	PLASTIC AP2211 EPOXY SURFACE COAT AND CASTING RESIN
67703	820	PLASTIC AP2220 HIGH-TEMP SURFACE EPOXY
67704	820	PLASTIC AP2308 EPOXY MASS CASTING
67705	821	PLASTIC AP2312 SURFACE CASTING
67706	821	PLASTIC AP2316 SURFACE CASTING
67707	821	PLASTIC AP2320 HI-TEMP EPOXY CASTING
67708	1,188	PLASTIC TP908 CARVABLE TOOLING PASTE
67709	1,188	PLASTIC TP-906 HARDSET TOOLING PASTE
67710	1,188	PLASTIC TP-903 HARDSET TOOLING PASTE
67711	821	PLASTIC AP3031 GLAZING COMPOUND
67712	1,025	PLASTIC PAXON AA55-80
67713	1,025	PLASTIC PAXON AA55-100
67714	1,025	PLASTIC PAXON AA50-180
67715	1,025	PLASTIC PAXON AA50-250
67716	1,025	PLASTIC PAXON AA-50-60
67717	1,025	PLASTIC PAXON AA-50-003
67718	814	PLASTIC AJ50-003
67719	1,026	PLASTIC PAXON AK53-004
67720	1,026	PLASTIC PAXON AG55-003
67721	1,026	PLASTIC PAXON AE50-003
67722	1,025	PLASTIC PAXON 3207
67723	1,025	PLASTIC PAXON 3204
67724	1,026	PLASTIC PAXON AA60-007
67725	1,026	PLASTIC PAXON AP60-007
67726	1,025	PLASTIC PAXON AA55-400
67727	1,026	PLASTIC PAXON AF40-003
67728	1,026	PLASTIC PAXON AC55-003
67729	1,026	PLASTIC PAXON AC40-003
67730	1,026	PLASTIC PAXON AB55-003
67731	1,026	PLASTIC PAXON AB50-003
67732	1,026	PLASTIC PAXON AB40-003
67733	1,026	PLASTIC PAXON BA50-100
67734	1,027	PLASTIC PAXON FP60-018
67735	1,025	PLASTIC PAXON 4700
67736	1,025	PLASTIC PAXON 3303
67737	1,025	PLASTIC PAXON 3205
67738	1,024	PLASTIC PAXON 3201
67739	1,026	PLASTIC PAXON AA60-003
67740	1,025	PLASTIC PAXON AA55-60
67741	837	PLASTIC CAPRON 8253
67742	837	PLASTIC CAPRON 8254
67743	838	PLASTIC CAPRON 8255
67744	837	PLASTIC CAPRON 8234G HS
67745	838	PLASTIC CAPRON 8266G HS
67746	838	PLASTIC CAPRON 8259
67747	838	PLASTIC CAPRON 8350
67748	837	PLASTIC CAPRON 8230G HS
67749	837	PLASTIC CAPRON 8233G HS
67750	838	PLASTIC CAPRON 8260
67751	838	PLASTIC CAPRON 8270
67752	837	PLASTIC CAPRON 8200
67753	837	PLASTIC CAPRON 8202
67754	837	PLASTIC CAPRON 8202L
67755	837	PLASTIC CAPRON 8202C
67756	837	PLASTIC CAPRON 8202CL
67757	838	PLASTIC CAPRON 8360
67758	837	PLASTIC CAPRON 8203G
67759	837	PLASTIC CAPRON 8221HS
67760	837	PLASTIC CAPRON 8220HS
67761	838	PLASTIC CAPRON 8276G HS
67762	837	PLASTIC CAPRON 8231G HS
67763	1,023	PLASTIC NYPEL 6033G
67764	932	PLASTIC HALAR FLOUROPOLYMER
67765	1,022	PLASTIC NYPEL 2314
67766	1,022	PLASTIC NYPEL 2314 FCAT
67767	1,022	PLASTIC NYPEL 2360
67768	932	PLASTIC HALAR 500
67769	932	PLASTIC HALAR 510

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006761 T ■

MATCD	PAGE	DESIGNATION
67770	1,022	PLASTIC NYPEL 2365G
67771	1,034	PLASTIC PETRA 130 FR
67773	1,034	PLASTIC PETRA 140
67774	1,034	PLASTIC PETRA 149
67775	1,034	PLASTIC PETRA 150
67776	1,034	PLASTIC PETRA 230
67777	1,098	PLASTIC RESINOL TYPE A
67778	1,098	PLASTIC RESINOL TYPE F
67779	1,098	PLASTIC RESINOL TYPE D
67780	1,131	PLASTIC STYRONOL
67781	855	PLASTIC CYGLAS 615
67782	855	PLASTIC CYGLAS 620M
67783	855	PLASTIC CYGLAS 620
67784	855	PLASTIC CYGLAS 610
67785	855	PLASTIC CYGLAS 600
67786	855	PLASTIC CYGLAS 605
67787	855	PLASTIC CYGLAS 508
67788	926	PLASTIC GLASKYD 1901
67789	926	PLASTIC GLASKYD 1902
67790	926	PLASTIC GLASKYD 1910
67791	926	PLASTIC GLASKYD 2201
67792	926	PLASTIC GLASKYD 3001H
67793	926	PLASTIC GLASKYD 4000
67794	926	PLASTIC GLASKYD 4001
67795	926	PLASTIC GLASKYD 4002
67796	799	PLASTIC 24082
67797	800	PLASTIC 260B1
67798	800	PLASTIC 290B1
67799	802	PLASTIC 360B1
67800	801	PLASTIC 3150B
67801	801	PLASTIC 3250B
67802	802	PLASTIC 3420B
67803	802	PLASTIC 3550B
67804	802	PLASTIC 403L3
67805	803	PLASTIC 404F3
67806	803	PLASTIC 408F3
67807	803	PLASTIC 4140B
67808	821	PLASTIC APCO 5321
67809	821	PLASTIC APCO 5323
67810	800	PLASTIC 2438/2180
67811	800	PLASTIC 2441/2180
67812	799	PLASTIC 2411/2311
67813	799	PLASTIC 2425/2310
67814	799	PLASTIC 2425/2305
67815	799	PLASTIC 2415/2180
67816	799	PLASTIC 2425/2324
67817	800	PLASTIC 2482/2192
67818	799	PLASTIC 2410/2183
67819	800	PLASTIC 2481/2161
67820	800	PLASTIC 2484/2192
67821	800	PLASTIC 2434/2310
67822	800	PLASTIC 2434/2320
67823	800	PLASTIC 2434/2330
67824	800	PLASTIC 2434/2323
67825	799	PLASTIC 2418/2140
67826	799	PLASTIC 2421/2140
67827	799	PLASTIC 2422/2140
67828	799	PLASTIC 2424/2174
67829	798	PLASTIC 2401/2180
67830	799	PLASTIC 2414/2180
67831	799	PLASTIC 2414/2320
67832	800	PLASTIC 2428/2330
67833	799	PLASTIC 2417/2180
67834	804	PLASTIC 5323 A/B
67835	798	PLASTIC 2405/2140
67836	798	PLASTIC 2403 A/B
67837	800	PLASTIC 2493/2164
67838	822	PLASTIC APCO 5393
67839	821	PLASTIC APCO 5290
67840	821	PLASTIC APCO 5293
67841	821	PLASTIC APCO 1475
67842	821	PLASTIC APCO 5303
67843	821	PLASTIC APCO 5313
67844	822	PLASTIC APCO 5823
67845	821	PLASTIC APCO 5363
67846	821	PLASTIC APCO 5314
67847	825	PLASTIC ARLOY 1000
67848	825	PLASTIC ARLOY 1100
67849	825	PLASTIC ARLOY 1200
67850	825	PLASTIC ARLOY 2000
67851	872	PLASTIC DYLARK 132
67852	872	PLASTIC DYLARK 138
67853	873	PLASTIC DYLARK 378
67854	872	PLASTIC DYLARK 232
67855	872	PLASTIC DYLARK 238
67856	872	PLASTIC DYLARK 238S
67857	872	PLASTIC DYLARK 238 F20A
67858	872	PLASTIC DYLARK 238S F20A
67859	872	PLASTIC DYLARK 240
67860	873	PLASTIC DYLARK 700
67861	872	PLASTIC DYLARK 250
67862	873	PLASTIC DYLARK 332
67863	873	PLASTIC DYLARK 338
67864	873	PLASTIC DYLARK 338S
67865	873	PLASTIC DYLARK 338S F20A
67866	873	PLASTIC DYLARK 350
67867	905	PLASTIC EZ-CAST 521 PLASTIC MOLDING COMPOUND
67868	905	PLASTIC EZ-CAST 588 PLASTIC MOLDING COMPOUND
67869	827	PLASTIC ASHLENE 528LW
67870	826	PLASTIC ASHLENE 525LD
67871	826	PLASTIC ASHLENE 527LD
67872	827	PLASTIC ASHLENE 528MS
67873	826	PLASTIC ASHLENE 528BR WO
67874	826	PLASTIC ASHLENE 520
67875	826	PLASTIC ASHLENE 521
67876	826	PLASTIC ASHLENE 522
67877	827	PLASTIC ASHLENE 528L 13G
67878	827	PLASTIC ASHLENE 528L 25G
67879	827	PLASTIC ASHLENE 528L 33G
67880	826	PLASTIC ASHLENE 525LD 13G

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006762 1

MATCD	PAGE	DESIGNATION
67881	828	PLASTIC ASHLENE 830L 13G
67882	828	PLASTIC ASHLENE 830L 33G
67883	827	PLASTIC ASHLENE 830L
67884	828	PLASTIC ASHLENE 830LN
67885	827	PLASTIC ASHLENE 735D
67886	827	PLASTIC ASHLENE 734D
67887	827	PLASTIC ASHLENE 738D
67888	827	PLASTIC ASHLENE 630
67889	827	PLASTIC ASHLENE 538
67890	827	PLASTIC ASHLENE 541
67891	828	PLASTIC ASHLENE 840
67892	827	PLASTIC ASHLENE 741
67893	827	PLASTIC ASHLENE 737
67894	923	PLASTIC GEON 82024
67895	925	PLASTIC GEON 8812
67896	925	PLASTIC GEON 8813
67897	923	PLASTIC GEIB 8815
67898	925	PLASTIC GEON 8814
67899	923	PLASTIC GEON 83008
67900	923	PLASTIC GEON 82611
67901	923	PLASTIC GEON 83741
67902	923	PLASTIC GEON 83718
67903	924	PLASTIC GEON 83794
67904	923	PLASTIC GEON 83457
67905	925	PLASTIC GEON 8883
67906	923	PLASTIC GEON 83421
67907	924	PLASTIC GEON 86153
67908	924	PLASTIC GEON 86154
67909	924	PLASTIC GEON 86155
67910	925	PLASTIC GEON 8857
67911	924	PLASTIC GEON 83791
67912	923	PLASTIC GEON 83463
67913	923	PLASTIC GEON 83332
67914	923	PLASTIC GEON 2042
67915	924	PLASTIC GEON 86143
67916	924	PLASTIC GEON 86135
67917	924	PLASTIC GEON 86144
67918	923	PLASTIC GEON 83700
67919	924	PLASTIC GEON 86188
67920	924	PLASTIC GEON 86054
67921	923	PLASTIC GEON 83528
67922	925	PLASTIC GEON 8804FR
67923	925	PLASTIC GEON CIM 87240
67924	925	PLASTIC GEON CIM 87241
67925	925	PLASTIC GEON CIM 87302
67926	925	PLASTIC GEON CIM 87317
67927	926	PLASTIC GEON CIM 87366
67928	926	PLASTIC GEON CIM 87371
67929	926	PLASTIC GEON CIM 87322
67930	925	PLASTIC GEON CIM 87242
67931	925	PLASTIC GEON CIM 87300
67932	926	PLASTIC GEON CIM 87319
67933	926	PLASTIC GEON CIM 87380
67934	925	PLASTIC GEON CIM 85856
67935	937	PLASTIC HOMOPOLYMER PVC RESIN VC54
67936	937	PLASTIC HOMOPOLYMER PVC RESIN VC58
67937	937	PLASTIC HOMOPOLYMER PVC RESIN VC95PM
67938	937	PLASTIC HOMOPOLYMER PVC RESIN VC100RE
67939	936	PLASTIC HOMOPOLYMER PVC RESIN VC100PM
67940	937	PLASTIC HOMOPOLYMER PVC RESIN VC47B
67941	937	PLASTIC HOMOPOLYMER PVC RESIN VC104PM
67942	937	PLASTIC HOMOPOLYMER PVC RESIN VC106PM
67943	850	PLASTIC COPOLYMER PVC RESIN VC113K
67944	850	PLASTIC COPOLYMER PVC RESIN VC113
67945	850	PLASTIC COPOLYMER PVC RESIN VC113R
67946	850	PLASTIC COPOLYMER PVC RESIN VC168
67947	850	PLASTIC COPOLYMER PVC RESIN VC171
67948	850	PLASTIC COPOLYMER PVC RESIN VC172
67949	831	PLASTIC BLENDING PVC RESINS VC265
67950	831	PLASTIC BLENDING PVC RESINS VC260C
67951	831	PLASTIC BLENDING PVC RESINS VC260S
67952	831	PLASTIC BLENDING PVC RESINS VC260SS
67953	1,024	PLASTIC PASTE PVC RESINS VC-405
67954	1,024	PLASTIC PASTE PVC RESINS 410M
67955	1,024	PLASTIC PASTE PVC RESINS VC-411
67956	1,024	PLASTIC PASTE PVC RESINS VC-436/VC-437
67957	1,024	PLASTIC PASTE PVC RESINS VC-440
67958	1,024	PLASTIC PASTE PVC RESINS VC1069
67959	1,188	PLASTIC TPR5190
67960	1,188	PLASTIC TPR5260
67961	1,188	PLASTIC TPR5280
67962	1,188	PLASTIC TPR5290
67963	1,188	PLASTIC TPR5470
67964	1,188	PLASTIC TPR5490
67965	1,189	PLASTIC TPR5595
67966	1,188	PLASTIC TPR5591
67967	1,188	PLASTIC TPR1900D
67968	1,188	PLASTIC TPR1720D
67969	830	PLASTIC BLANE 309
67970	830	PLASTIC BLANE 375
67971	831	PLASTIC BLANE 8105
67972	831	PLASTIC BLANE 830
67973	831	PLASTIC BLANE 851
67974	830	PLASTIC BLANE 2150
67975	830	PLASTIC BLANE 2153
67976	830	PLASTIC BLANE 2202
67977	830	PLASTIC BLANE 2234
67978	830	PLASTIC BLANE 2249
67979	831	PLASTIC BLANE 7191
67980	831	PLASTIC BLANE 8100
67981	831	PLASTIC BLANE 9148
67982	831	PLASTIC BLANE 9202-1
67983	1,053	PLASTIC POLY EMULSION 261 A35
67984	1,054	PLASTIC POLY EMULSION 392 N35
67985	1,053	PLASTIC POLY EMULSION 325 N35
67986	1,053	PLASTIC POLY EMULSION 330 N35
67987	1,053	PLASTIC POLY EMULSION 392 A25
67988	1,053	PLASTIC POLY EMULSION 392 LE30
67989	1,053	PLASTIC POLY EMULSION 392 N25
67990	1,053	PLASTIC POLY EMULSION 392 C30

MSFC-HDBK-527 REV F 9999942 0006763 3

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
67991	1,053	PLASTIC POLY EMULSION 316 N30
67992	1,053	PLASTIC POLY EMULSION 153 N35
67993	1,053	PLASTIC POLY EMULSION 121 N30
67994	1,054	PLASTIC POLY EMULSION 540 N30
67995	1,054	PLASTIC POLY EMULSION 540 N40
67996	1,054	PLASTIC POLY EMULSION 540 A25
67997	1,054	PLASTIC POLY EMULSION 629 A30
67998	1,054	PLASTIC POLY EMULSION 629 N04
67999	1,053	PLASTIC POLY EMULSION 10 N30
68000	1,054	PLASTIC POLY EMULSION 656 A25
68001	1,053	PLASTIC POLY EMULSION 371 N30
68002	1,054	PLASTIC POLY EMULSION 43 N40
68003	841	PLASTIC CHEMCOR EMULSION 2-67A
68004	1,033	PLASTIC PEN CLEAR
68005	1,034	PLASTIC PEN-1031
68006	1,023	PLASTIC OPACIFIER 341
68007	862	PLASTIC DISPERSION 8-31B
68008	1,024	PLASTIC PARIFIN EMULSION 135-40
68009	841	PLASTIC CHEMCOR ZAC
68010	889	PLASTIC EMULSION XL20
68011	1,041	PLASTIC PFA
68012	904	PLASTIC ETFE
68013	877	PLASTIC ECTFE
68014	852	PLASTIC CTFE
68015	924	PLASTIC GEON 87237
68016	924	PLASTIC GEON 87239
68018	924	PLASTIC GEON 87341
68019	925	PLASTIC GEON 87342
68024	924	PLASTIC GEON 87321
68027	36	ADHESIVE ARALDITE 465 A80
68028	1,218	PLASTIC UNICHEM 9814
68029	1,216	PLASTIC UNICHEM 8715
68030	1,215	PLASTIC UNICHEM 8560
68031	1,213	PLASTIC UNICHEM 8190FR-1
68032	1,213	PLASTIC UNICHEM 8180FR-1
68033	1,207	PLASTIC UNICHEM 7000
68034	1,209	PLASTIC UNICHEM 7500
68035	1,211	PLASTIC UNICHEM 8000
68036	1,214	PLASTIC UNICHEM 8500
68037	1,216	PLASTIC UNICHEM 9000
68038	1,217	PLASTIC UNICHEM 9500
68039	1,204	PLASTIC UNICHEM 4543
68040	1,204	PLASTIC UNICHEM 4875
68041	1,205	PLASTIC UNICHEM 5543
68042	1,205	PLASTIC UNICHEM 5545
68043	1,205	PLASTIC UNICHEM 5790
68044	1,207	PLASTIC UNICHEM 6575
68045	1,208	PLASTIC UNICHEM 7075
68046	1,210	PLASTIC UNICHEM 7575
68047	1,213	PLASTIC UNICHEM 8090C
68048	1,216	PLASTIC UNICHEM 8804
68049	1,217	PLASTIC UNICHEM 9614
68050	1,208	PLASTIC UNICHEM 7033
68051	1,212	PLASTIC UNICHEM 8033
68052	1,215	PLASTIC UNICHEM 8533
68053	1,216	PLASTIC UNICHEM 9033
68054	1,218	PLASTIC UNICHEM 9813 (BLACK,WHITE,BROWN)
68055	1,207	PLASTIC UNICHEM 6742
68056	1,207	PLASTIC UNICHEM 6743
68057	1,209	PLASTIC UNICHEM 7342
68058	1,210	PLASTIC UNICHEM 7580
68059	1,212	PLASTIC UNICHEM 8080
68060	1,212	PLASTIC UNICHEM 8083
68061	1,202	PLASTIC UNICHEM 4060
68062	1,202	PLASTIC UNICHEM 4060A
68063	1,202	PLASTIC UNICHEM 4075
68064	1,202	PLASTIC UNICHEM 4075H
68065	1,202	PLASTIC UNICHEM 40-105
68066	1,202	PLASTIC UNICHEM 4114
68067	1,203	PLASTIC UNICHEM 4195
68068	1,204	PLASTIC UNICHEM 5433
68069	1,202	PLASTIC UNICHEM 4160
68070	1,203	PLASTIC UNICHEM 4160C
68071	1,202	PLASTIC UNICHEM 4160 LT/FR-1
68072	1,203	PLASTIC UNICHEM 4260-75
68073	1,203	PLASTIC UNICHEM 4260-80
68074	1,203	PLASTIC UNICHEM 4260-90
68075	1,211	PLASTIC UNICHEM 8005
68076	1,211	PLASTIC UNICHEM 8005C
68077	1,211	PLASTIC UNICHEM 8006 MG
68078	1,212	PLASTIC UNICHEM 8060
68080	1,215	PLASTIC UNICHEM 8580
68081	1,213	PLASTIC UNICHEM 8085
68082	1,213	PLASTIC UNICHEM 8190
68083	1,213	PLASTIC UNICHEM 8205
68084	1,215	PLASTIC UNICHEM 8705
68085	1,216	PLASTIC UNICHEM 9005
68086	1,217	PLASTIC UNICHEM 9805
68087	1,200	PLASTIC UNICHEM 105
68088	1,204	PLASTIC UNICHEM 5376
68089	1,209	PLASTIC UNICHEM 7444
68090	1,209	PLASTIC UNICHEM 7444D
68091	1,206	PLASTIC UNICHEM 6476
68092	804	PLASTIC 5311-19
68093	1,204	PLASTIC UNICHEM 5311-38
68094	1,205	PLASTIC UNICHEM 5812
68095	1,208	PLASTIC UNICHEM 7012
68096		DELETED SEE 68095
68097	1,201	PLASTIC UNICHEM 1280G-015
68098	1,202	PLASTIC UNICHEM 4012G-015
68099	1,204	PLASTIC UNICHEM 5012G-015
68100	1,205	PLASTIC UNICHEM 6012G-015
68101	1,207	PLASTIC UNICHEM 6512G-015
68102	1,207	PLASTIC UNICHEM 6812G-015
68103	1,208	PLASTIC UNICHEM 7012G-015
68104	1,209	PLASTIC UNICHEM 7512G-015
68105	1,210	PLASTIC UNICHEM 7812G-015
68106	1,212	PLASTIC UNICHEM 8012G-015
68107	1,214	PLASTIC UNICHEM 8312G-015
68108	1,215	PLASTIC UNICHEM 8512G-015

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006764 5

MATCD	PAGE	DESIGNATION
68109	1,216	PLASTIC UNICHEM 9012G-015
68110	1,217	PLASTIC UNICHEM 9512G-015
68111	1,217	PLASTIC UNICHEM 9612G-015
68112	1,218	PLASTIC UNICHEM 9811-015
68113	1,218	PLASTIC UNICHEM 9812G-015
68114	1,201	PLASTIC UNICHEM 1116G-015
68115	1,211	PLASTIC UNICHEM 7815
68116	1,202	PLASTIC UNICHEM 4011
68117	1,204	PLASTIC UNICHEM 5011
68118	1,204	PLASTIC UNICHEM 5511
68119	1,205	PLASTIC UNICHEM 6011
68120	1,206	PLASTIC UNICHEM 6511
68121	1,207	PLASTIC UNICHEM 6811
68122	1,208	PLASTIC UNICHEM 7011
68123	1,209	PLASTIC UNICHEM 7511
68124	1,210	PLASTIC UNICHEM 7811
68125	1,211	PLASTIC UNICHEM 8011
68126	1,214	PLASTIC UNICHEM 8311
68127	1,214	PLASTIC UNICHEM 8511
68128	1,216	PLASTIC UNICHEM 9011
68129	1,217	PLASTIC UNICHEM 9511
68130	1,217	PLASTIC UNICHEM 9611
68131	1,217	PLASTIC UNICHEM 9811
68132	1,218	PLASTIC UNICHEM 9904
68133	1,201	PLASTIC UNICHEM 1104
68134	1,201	PLASTIC UNICHEM 1114
68135	1,201	PLASTIC UNICHEM 1116
68137	1,215	PLASTIC UNICHEM 8705-FR
68138	1,216	PLASTIC UNICHEM 8990
68140	1,217	PLASTIC UNICHEM 9172C
68141	1,211	PLASTIC UNICHEM 8005-90
68142	1,210	PLASTIC UNICHEM 7805 (CLEAR)
68143	1,210	PLASTIC UNICHEM 7805
68144	1,210	PLASTIC UNICHEM 7533
68145	1,203	PLASTIC UNICHEM 4261-80
68146	1,203	PLASTIC UNICHEM 4260-85
68147	1,203	PLASTIC UNICHEM 4260A-66
68148	1,204	PLASTIC UNICHEM 5376FFR
68149	1,206	PLASTIC UNICHEM 6193F
68150	1,203	PLASTIC UNICHEM 4260-95
68151	1,203	PLASTIC UNICHEM 4196
68153	1,203	PLASTIC UNICHEM 4160LT
68154		DELETED SEE 68065
68155	1,202	PLASTIC UNICHEM 4075H FR
68156	1,202	PLASTIC UNICHEM 3879
68157	1,202	PLASTIC UNICHEM 3876
68159	1,214	PLASTIC UNICHEM 84-421D
68160	1,214	PLASTIC UNICHEM 84-369
68161	1,214	PLASTIC UNICHEM 84-209C
68162	1,200	PLASTIC UNICHEM 10015-XRAY
68163	1,218	PLASTIC UNICHEM 9904-03
68164	1,218	PLASTIC UNICHEM 9811-15
68165	1,216	PLASTIC UNICHEM 9001C-015
68166	1,215	PLASTIC UNICHEM 8588
68167	1,215	PLASTIC UNICHEM 8681
68168	1,215	PLASTIC UNICHEM 8711A-02
68169	1,217	PLASTIC UNICHEM 9712A-02-HS
68170	1,218	PLASTIC UNICHEM CUM8882
68171	1,214	PLASTIC UNICHEM 8311A-02
68172	1,214	PLASTIC UNICHEM 8312B-02
68173	1,214	PLASTIC UNICHEM 8511A-02
68174	1,215	PLASTIC UNICHEM 8512N-02
68175	1,214	PLASTIC UNICHEM 8311A
68176	1,212	PLASTIC UNICHEM 8011AG-015
68177	1,212	PLASTIC UNICHEM 8011K-02
68178	1,212	PLASTIC UNICHEM 8011-02
68179	1,212	PLASTIC UNICHEM 8011A-02
68180	1,212	PLASTIC UNICHEM 8011G-015
68181	1,212	PLASTIC UNICHEM 8011 RADIO-OPAQUE
68182	1,212	PLASTIC UNICHEM 8012
68183	1,213	PLASTIC UNICHEM 8090
68184	1,210	PLASTIC UNICHEM 7813
68185	1,211	PLASTIC UNICHEM 7815G-015
68186	1,210	PLASTIC UNICHEM 7811-30
68187	1,210	PLASTIC UNICHEM 7712-G-015
68188	1,210	PLASTIC UNICHEM 7712F-NBBM
68190	1,209	PLASTIC UNICHEM 7511B-02
68191	1,209	PLASTIC UNICHEM 7411-0
68192	1,209	PLASTIC UNICHEM 7233H
68193	1,208	PLASTIC UNICHEM 7099
68194	1,208	PLASTIC UNICHEM 7012C-02
68195	1,208	PLASTIC UNICHEM 7011CZ-02
68196	1,208	PLASTIC UNICHEM 7011G-015
68197	1,207	PLASTIC UNICHEM 6812-02
68198	1,207	PLASTIC UNICHEM 6811-02 BUSCH
68199	1,206	PLASTIC UNICHEM 6512
68200	1,206	PLASTIC UNICHEM 6511A-02
68201	1,206	PLASTIC UNICHEM 6511-02
68202	1,206	PLASTIC UNICHEM 6111B
68203	1,206	PLASTIC UNICHEM 6111A
68204	1,205	PLASTIC UNICHEM 6022 NATURAL
68205	1,205	PLASTIC UNICHEM 6014 D FOAM
68206	1,205	PLASTIC UNICHEM 6011G-015
68207	1,205	PLASTIC UNICHEM 6011A-02
68208	1,205	PLASTIC UNICHEM 5811
68209	1,205	PLASTIC UNICHEM 5612
68210	1,204	PLASTIC UNICHEM 5511-02
68212	1,204	PLASTIC UNICHEM 5211
68213	1,204	PLASTIC UNICHEM 5012G-05
68214	1,203	PLASTIC UNICHEM 4511
68215	1,203	PLASTIC UNICHEM 4170
68216	1,201	PLASTIC UNICHEM 1280A-02
68217	1,201	PLASTIC UNICHEM 1115G-05
68218	1,201	PLASTIC UNICHEM 1114G-05
68219	1,201	PLASTIC UNICHEM 1104-05
68220	1,200	PLASTIC UNICHEM 1015G-05
68221	1,200	PLASTIC UNICHEM 1011G-015
68222	1,211	PLASTIC UNICHEM 80-111K
68223	1,211	PLASTIC UNICHEM 7933H
68224	1,209	PLASTIC UNICHEM 75-103B

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006765 7 ■

MATCD	PAGE	DESIGNATION
68225	1,218	PLASTIC UNICHEM AG8757E
68226	1,218	PLASTIC UNICHEM 9833
68227	1,218	PLASTIC UNICHEM 9813
68228	1,215	PLASTIC UNICHEM 8614
68229	1,217	PLASTIC UNICHEM 9554-F4
68230	1,217	PLASTIC UNICHEM 9511A-02
68231	1,217	PLASTIC UNICHEM 9314A
68232	1,216	PLASTIC UNICHEM 9034A-FRLS
68233	1,216	PLASTIC UNICHEM 9012N-02
68234	1,216	PLASTIC UNICHEM 9003
68235		DELETED SEE 68037
68236	1,216	PLASTIC UNICHEM 8733
68237	1,215	PLASTIC UNICHEM 8703
68238	1,215	PLASTIC UNICHEM 8634
68239	1,215	PLASTIC UNICHEM 8562
68240	1,213	PLASTIC UNICHEM 8200 FR WHITE
68241	1,213	PLASTIC UNICHEM 8200FR
68242	1,214	PLASTIC UNICHEM 8511-02
68243	1,214	PLASTIC UNICHEM 8299
68244	1,213	PLASTIC UNICHEM 8092
68245	1,216	PLASTIC UNICHEM 8901
68247	1,213	PLASTIC UNICHEM 8093 NATURAL
68248	1,212	PLASTIC UNICHEM 8034
68249	1,212	PLASTIC UNICHEM 8012N-02
68250	1,211	PLASTIC UNICHEM 8000-02
68251	1,211	PLASTIC UNICHEM 8000 FR-UV
68252	1,211	PLASTIC UNICHEM 7849
68253	1,211	PLASTIC UNICHEM 7834
68254	1,210	PLASTIC UNICHEM 7810
68255	1,210	PLASTIC UNICHEM 7588 CLEAR BLUE
68256	1,210	PLASTIC UNICHEM 7533A FR
68257	1,209	PLASTIC UNICHEM 7503
68259		DELETED SEE 68034
68260	1,209	PLASTIC UNICHEM 7380 CLEAR
68261	1,209	PLASTIC UNICHEM 7342 CLEAR
68262	1,209	PLASTIC UNICHEM 7305
68263	1,208	PLASTIC UNICHEM 7233
68264	1,208	PLASTIC UNICHEM 7224B
68265	1,218	PLASTIC UNICHEM AA7093
68266	1,217	PLASTIC UNICHEM 9090
68267	1,208	PLASTIC UNICHEM 7074
68269	1,207	PLASTIC UNICHEM 7003
68270	1,208	PLASTIC UNICHEM 7003 WHITE
68271	1,207	PLASTIC UNICHEM 6812A-02
68272	1,207	PLASTIC UNICHEM 6743 CLEAR
68273	1,207	PLASTIC UNICHEM 6576
68274	1,207	PLASTIC UNICHEM 6574
68275	1,206	PLASTIC UNICHEM 6093
68276	1,206	PLASTIC UNICHEM 6507
68277	1,206	PLASTIC UNICHEM 6500
68278	1,206	PLASTIC UNICHEM 6283
68279	1,206	PLASTIC UNICHEM 6091
68280	1,206	PLASTIC UNICHEM 6033
68281	1,205	PLASTIC UNICHEM 5790A
68284	1,204	PLASTIC UNICHEM 5500
68285	1,204	PLASTIC UNICHEM 5160-40
68286	1,202	PLASTIC UNICHEM 1416-05
68287	1,201	PLASTIC UNICHEM 1317
68288	1,201	PLASTIC UNICHEM 1316-05
68289	1,201	PLASTIC UNICHEM 1314 NATURAL
68290	1,200	PLASTIC UNICHEM 1080G
68291	1,201	PLASTIC UNICHEM 1304G
68292	1,214	PLASTIC UNICHEM 85-268F
68294	1,213	PLASTIC UNICHEM 82-378D
68295	1,218	PLASTIC UNICHEM 9813 (GREENS)
68296	849	PLASTIC COMALLOY 660-3033
68297	849	PLASTIC COMALLOY 660-3043
68298	848	PLASTIC COMALLOY 640-3033
68299	848	PLASTIC COMALLOY 640-3050
68300	848	PLASTIC COMALLOY 640-2250
68301	849	PLASTIC COMALLOY 710-3030
68302	849	PLASTIC COMALLOY 710-3050
68303	849	PLASTIC COMALLOY 710-2250
68304	849	PLASTIC COMALLOY 740-3020
68305	849	PLASTIC COMALLOY 740-3040
68306	849	PLASTIC COMALLOY 660-3050
68307	848	PLASTIC COMALLOY 640-3020
68308	848	PLASTIC COMALLOY 640-3043
68309	848	PLASTIC COMALLOY 640-2140
68310	848	PLASTIC COMALLOY 640-2355
68312	849	PLASTIC COMALLOY 710-2355
68313	849	PLASTIC COMALLOY 710-2140
68314	849	PLASTIC COMALLOY 740-3030
68315	844	PLASTIC COMALLOY 220-3010
68316	844	PLASTIC COMALLOY 220-3030
68317	845	PLASTIC COMALLOY 240-3020
68318	845	PLASTIC COMALLOY 240-3040
68319	845	PLASTIC COMALLOY 260-3030
68320	845	PLASTIC COMALLOY 310-3015
68321	845	PLASTIC COMALLOY 410-3015
68322	846	PLASTIC COMALLOY 410-3045
68323	845	PLASTIC COMALLOY 410-2140
68324	845	PLASTIC COMALLOY 410-2355
68325	846	PLASTIC COMALLOY 410-3030-100
68326	845	PLASTIC COMALLOY 410-2140-100
68327	846	PLASTIC COMALLOY 510-3010
68328	846	PLASTIC COMALLOY 510-3030
68329	846	PLASTIC COMALLOY 510-1515
68330	846	PLASTIC COMALLOY 515-1000
68331	847	PLASTIC COMALLOY 610-3020
68332	847	PLASTIC COMALLOY 610-3043
68333	846	PLASTIC COMALLOY 610-2140
68334	847	PLASTIC COMALLOY 610-2355
68335	848	PLASTIC COMALLOY 620-3020
68336	848	PLASTIC COMALLOY 620-3050
68337	847	PLASTIC COMALLOY 620-2140
68338	847	PLASTIC COMALLOY 620-2355
68339	848	PLASTIC COMALLOY 620-3020-100
68340	848	PLASTIC COMALLOY 620-3043-100
68341	848	PLASTIC COMALLOY 660-3013

MSFC-HDBK-527 REV F 9999942 0006766 9

Information Handling Services, 2000

NON-METALS DESIGNATIONS BY MATERIAL CODE

MATCD	PAGE	DESIGNATION
68342	844	PLASTIC COMALLOY 220-3020
68343	844	PLASTIC COMALLOY 220-3040
68344	845	PLASTIC COMALLOY 240-3030
68345	845	PLASTIC COMALLOY 260-3020
68346	845	PLASTIC COMALLOY 310-3010
68347	845	PLASTIC COMALLOY 310-3020
68348	846	PLASTIC COMALLOY 410-3030
68349	846	PLASTIC COMALLOY 410-3055
68350	845	PLASTIC COMALLOY 410-2250
68351	846	PLASTIC COMALLOY 410-3015-100
68352	846	PLASTIC COMALLOY 410-3045-100
68353	845	PLASTIC COMALLOY 410-2250-100
68354	846	PLASTIC COMALLOY 510-3024
68355	846	PLASTIC COMALLOY 510-3040
68356	846	PLASTIC COMALLOY 510-2615
68357	847	PLASTIC COMALLOY 610-3013
68358	847	PLASTIC COMALLOY 610-3033
68359	847	PLASTIC COMALLOY 610-3050
68360	847	PLASTIC COMALLOY 610-2250
68361	847	PLASTIC COMALLOY 620-3013
68362	848	PLASTIC COMALLOY 620-3043
68363	847	PLASTIC COMALLOY 620-1540
68364	847	PLASTIC COMALLOY 620-2250
68365	847	PLASTIC COMALLOY 620-3013-100
68366	848	PLASTIC COMALLOY 620-3033-100
68367	847	PLASTIC COMALLOY 620-2140-100
68368	849	PLASTIC COMALLOY 660-3020
68370	843	PLASTIC COMALLOY 110-3030
68371	843	PLASTIC COMALLOY 110-1120
68372	843	PLASTIC COMALLOY 110-1220
68373	396	COMALLOY 110-1520
68374	843	PLASTIC COMALLOY 110-1540
68375	843	PLASTIC COMALLOY 110-3010
68376	843	PLASTIC COMALLOY 110-3020
68377	843	PLASTIC COMALLOY 110-3040
68378	843	PLASTIC COMALLOY 110-1140
68379	843	PLASTIC COMALLOY 110-1240
68381	844	PLASTIC COMALLOY 140-3030
68382	844	PLASTIC COMALLOY 140-3010
68383		DELETED SEE 68381
68384	843	PLASTIC COMALLOY 140-2140
68385	844	PLASTIC COMALLOY 140-2355
68386	844	PLASTIC COMALLOY 170-3030
68387	844	PLASTIC COMALLOY 210-3020
68388	843	PLASTIC COMALLOY 120-2430
68389	851	PLASTIC CP41
68390	851	PLASTIC CP51
68391	851	PLASTIC CP61
68392	851	PLASTIC CP80
68393	852	PLASTIC CP81
68394	852	PLASTIC CP82
68395	850	PLASTIC COPO 1507
68396	897	PLASTIC EPSYN 70A
68397	843	PLASTIC COMALLOY 130-3020
68398	843	PLASTIC COMALLOY 130-3040
68399	844	PLASTIC COMALLOY 140-3020
68400	844	PLASTIC COMALLOY 140-3040
68401	843	PLASTIC COMALLOY 140-2250
68402	844	PLASTIC COMALLOY 170-3020
68403	844	PLASTIC COMALLOY 170-3040
68404	844	PLASTIC COMALLOY 210-3030
68405	826	PLASTIC AS15CF1000
68406	828	PLASTIC AT20GF
68407	828	PLASTIC AT30GF
68408	828	PLASTIC AT40GF
68409	1,010	PLASTIC NY-20GF
68410	1,010	PLASTIC NY-40GF
68411	1,010	PLASTIC NY-60GF
68412	997	PLASTIC NN10GF
68413	997	PLASTIC NN30GF
68414	997	PLASTIC NN50GF
68415	997	PLASTIC NN20CF
68416	997	PLASTIC NN40CF
68417	996	PLASTIC NI20GF
68418	996	PLASTIC NI40GF
68419	997	PLASTIC NL20GF
68420	997	PLASTIC NL40GF
68421	997	PLASTIC NL60GF
68422	996	PLASTIC NH30GF
68423	996	PLASTIC NJ30GF
68424	1,028	PLASTIC PC-30GF
68425	820	PLASTIC AN20GF
68426	820	PLASTIC AN30GF
68427	820	PLASTIC AN40GF
68428	1,010	PLASTIC NY-10GF
68429	1,010	PLASTIC NY-30GF
68430	1,010	PLASTIC NY-50GF
68431	1,010	PLASTIC NY-30CF
68432	997	PLASTIC NN20GF
68433	997	PLASTIC NN40GF
68434	998	PLASTIC NN60GF
68435	997	PLASTIC NN30CF
68436	998	PLASTIC NN60CF1000
68437	996	PLASTIC NI30GF
68438	997	PLASTIC NL10GF
68439	997	PLASTIC NL30GF
68440	997	PLASTIC NL50GF
68441	996	PLASTIC NH20GF
68442	996	PLASTIC NH40GF
68443	1,027	PLASTIC PC-20GF
68444	1,028	PLASTIC PC-40GF
68445	1,027	PLASTIC PC-000/5T
68446	1,027	PLASTIC PC-000/15T
68447	1,027	PLASTIC PC-20GF/15T
68448	1,028	PLASTIC PC-40GF/15T
68449	1,027	PLASTIC PC-20CF
68450	1,028	PLASTIC PC-40CF
68451	1,027	PLASTIC PC-10CF/000
68452	1,027	PLASTIC PC-30CF/20
68453	899	PLASTIC ES20GF/000

MSFC-HDBK-527 REV F ■ 9999942 0006767 0 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
68454	899	PLASTIC ES40GF/000
68455	899	PLASTIC ES30CF/000
68456	1,117	PLASTIC SF-40GF
68457	1,116	PLASTIC SF-30CF
68458	1,117	PLASTIC SF-30GF/15T
68459	1,116	PLASTIC SF-30CF/15T
68460	1,040	PLASTIC PF-30GF
68461	1,040	PLASTIC PF-000/15T
68462	1,040	PLASTIC PF-20GF/15T
68463	1,040	PLASTIC PF-30CF
68464	1,091	PLASTIC PS-15GF/000
68465	1,091	PLASTIC PS-30GF 30% GLASS
68466	1,091	PLASTIC PS-30GF/000 FR
68467	1,041	PLASTIC PI 30GF/000
68468	1,041	PLASTIC PI-30 CF/000
68469	1,041	PLASTIC PK-20GF/000
68470	1,041	PLASTIC PK-40CF/000
68471	1,027	PLASTIC PC-000/10T
68472	1,027	PLASTIC PC-000/20T
68473	1,028	PLASTIC PC-30GF/15T
68474	1,027	PLASTIC PC-30CF
68475	1,027	PLASTIC PC-10GF/000 FR
68476	1,027	PLASTIC PC-20CF/15T
68477	1,042	PLASTIC PL-20 NCF/000 FCR
68478	897	PLASTIC EPSYN 4506
68479	899	PLASTIC ES39GF/000
68480	900	PLASTIC ES7CF/000
68481	1,117	PLASTIC SF-30GF
68482	1,116	PLASTIC SF-20CF
68483	1,117	PLASTIC SF-40CF
68484	1,116	PLASTIC SF-20CF/000
68485	1,040	PLASTIC PF-20GF
68486	1,041	PLASTIC PF-40GF
68487	1,040	PLASTIC PF-10GF/15T
68488	1,041	PLASTIC PF-30GF/000
68489	1,091	PLASTIC PS-20GF/000
68490	1,091	PLASTIC PS-10GF/000
68491	1,091	PLASTIC PS-15GF/000 GR
68492	1,041	PLASTIC PI 20GF/000
68493	1,041	PLASTIC PI 40GF/000
68494	1,041	PLASTIC PI-40CF/000
68495	1,078	PLASTIC PR-20CF/000
68496	897	PLASTIC EPSYN 5508
68497	897	PLASTIC EPSYN 7506
68498	1,023	PLASTIC NYSYN 28-7XL
68499	897	PLASTIC EPSYN 40A
68500	897	PLASTIC EPSYN 2506
68501	897	PLASTIC EPSYN 4906
68502	850	PLASTIC COSDEN 500
68503	851	PLASTIC COSDEN 525
68504	851	PLASTIC COSDEN 535
68505	851	PLASTIC COSDEN 550
68506	851	PLASTIC COSDEN 560
68507	851	PLASTIC COSDEN 625
68508	851	PLASTIC COSDEN 680
68509	851	PLASTIC COSDEN 740
68510	851	PLASTIC COSDEN 825
68511	851	PLASTIC COSDEN 825E
68512	851	PLASTIC COSDEN 945
68513	1,020	PLASTIC NYLON 404
68514	1,020	PLASTIC NYLON 409
68515	1,020	PLASTIC NYLON 451
68516	1,020	PLASTIC NYLON 452
68517	1,020	PLASTIC NYLON 453
68518	1,020	PLASTIC NYLON 454
68519	1,021	PLASTIC NYLON 601
68520	1,021	PLASTIC NYLON 600
68521	1,021	PLASTIC NYLON 607
68522	1,021	PLASTIC NYLON 603
68523	1,021	PLASTIC NYLON 609
68524	1,021	PLASTIC NYLON 615
68525	1,022	PLASTIC NYLON NX 2011
68526	1,022	PLASTIC NYLON NX 6200
68527	1,022	PLASTIC NYLON NX 5703
68528	1,020	PLASTIC NYLON 401
68529	1,020	PLASTIC NYLON 402
68530	905	PLASTIC EXOLITE DOUBLE SKINNED ACRYLIC SHEET
68531	905	PLASTIC EXOLITE DOUBLE SKINNED POLYCARBONATE SHEET
68532	874	PLASTIC E50047
68533	954	PLASTIC LE6328/HD3201
68534	954	PLASTIC LE5301/HD3201
68535	954	PLASTIC LE4341/1HD3201
68536	954	PLASTIC LE6019/HD3469
68537	954	PLASTIC LE1006/HD3831
68538	954	PLASTIC LE5301/1HD3824
68539	1,034	PLASTIC PENNLON UHMWPE
68540	850	PLASTIC COMPOUND 954
68541	1,020	PLASTIC NYLON 6
68543	1,021	PLASTIC NYLON 6/6 10% GLASS
68544	1,020	PLASTIC NYLON 6.6 33% GLASS
68545	1,021	PLASTIC NYLON 6/6 MINERAL FILLED
68546	1,020	PLASTIC NYLON 6.6 30% CF 15% TFE
68547	1,189	PLASTIC TROGAMID
68548	810	PLASTIC ACETAL 10% GLASS
68549	810	PLASTIC ACETAL 20% GLASS
68550	858	PLASTIC DELRIN 907F
68551	1,114	PLASTIC RULON LD, PTFE
68552	1,114	PLASTIC RULON J, PTFE
68553	1,113	PLASTIC RULON 123, PTFE
68554	1,114	PLASTIC RULON W-2, PTFE
68555	810	PLASTIC ACETAL 21% TFE
68556	1,065	PLASTIC POLYSULFONE
68557	1,066	PLASTIC POLYSULFONE 30% CF
68558	1,055	PLASTIC POLYCARBONATE
68559	1,055	PLASTIC POLYCARBONATE 20% GLASS
68560	1,027	PLASTIC PBT (RYNITE)
68561	1,056	PLASTIC POLYETHERSULFONE 30% GLASS
68562	1,056	PLASTIC POLYETHERSULFONE 30% CF
68563	1,078	PLASTIC PPO
68564	1,062	PLASTIC POLYPROPYLENE

MSFC-HDBK-527 REV F 9999942 0006768 2

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
68565	1,062	PLASTIC POLYPROPYLENE 10% GLASS
68566	1,062	PLASTIC POLYPROPYLENE 30% GLASS
68567	1,114	PLASTIC RULON LOP-A, PTFE
68568	1,114	PLASTIC RULON E, PTFE
68569	1,114	PLASTIC RULON G-65, PTFE
68570	862	PLASTIC DIXON COMPOUND 7035 PTFE
68571	862	PLASTIC DIXON COMPOUND 201 PTFE
68572	797	PLASTIC 15% CARBON, PTFE
68574	798	PLASTIC 20% GLASS, 5% MOS2, PTFE
68575	1,188	PLASTIC TORLON 5030
68576	1,033	PLASTIC PEEK
68577	1,193	PLASTIC ULTEM 2100
68578	1,193	PLASTIC ULTEM 2300
68579	1,116	PLASTIC RYTON R-8
68580	1,114	PLASTIC RULON II
68581	986	PLASTIC MELOIN P1 POLYIMIDE
68582	986	PLASTIC MELOIN P1-30X POLYIMIDE
68583	986	PLASTIC MELOIN P1-15Y POLYIMIDE
68584	985	PLASTIC MELOIN 9000
68588	1,093	PLASTIC PVDF
68589	1,193	PLASTIC ULTEM 2200
68590	1,115	PLASTIC RYTON 15% TFE 30% CF
68591	1,137	PLASTIC TEFLON 62 TFE
68592	1,137	PLASTIC TEFLON 67 TFE
68593	1,138	PLASTIC TEFLON TFE 66
68594	1,137	PLASTIC TEFLON 6C PTFE
68595	1,137	PLASTIC TEFLON FEP 100
68596	1,138	PLASTIC TEFLON TFE 8B
68597	1,138	PLASTIC TEFLON TFE 9B
68598	1,137	PLASTIC TEFLON TFE 64
68599	1,137	PLASTIC TEFLON TFE 160
68600	1,137	PLASTIC TEFLON TFE 60
68601	1,138	PLASTIC TEFLON TFE 65
68602	1,137	PLASTIC TEFLON FEP 140
68603	1,138	PLASTIC TEFLON TFE 8A
68604	1,138	PLASTIC TEFLON TFE 8
68605	856	PLASTIC DELRIN 100
68606	857	PLASTIC DELRIN 100F
68607	857	PLASTIC DELRIN 150SA
68608	857	PLASTIC DELRIN 100CL
68609	858	PLASTIC DELRIN 507
68610	857	PLASTIC DELRIN 107
68611	857	PLASTIC DELRIN 100D
68612	857	PLASTIC DELRIN 100AF
68613	858	PLASTIC DELRIN 550SA
68614	857	PLASTIC DELRIN 500F
68615	857	PLASTIC DELRIN 500HP
68616	858	PLASTIC DELRIN 510AF
68617	858	PLASTIC DELRIN 570
68618	858	PLASTIC DELRIN 900
68619	858	PLASTIC DELRIN 900D
68620	858	PLASTIC DELRIN 900HP
68621	857	PLASTIC DELRIN 100ST
68622	857	PLASTIC DELRIN 500D
68623	857	PLASTIC DELRIN 500AF
68624	857	PLASTIC DELRIN 500CL
68625	858	PLASTIC DELRIN 577
68626	858	PLASTIC DELRIN 900F
68627	857	PLASTIC DELRIN 200PL
68628	858	PLASTIC DELRIN 500T
68629	1,240	PLASTIC ZYTEL 101
68630	1,241	PLASTIC ZYTEL 42
68631	1,240	PLASTIC ZYTEL 101L
68632	1,240	PLASTIC ZYTEL 105
68633	1,240	PLASTIC ZYTEL 133C
68634	1,241	PLASTIC ZYTEL 408C
68635	1,240	PLASTIC ZYTEL 158C
68636	1,241	PLASTIC ZYTEL 91 HS
68637	1,241	PLASTIC ZYTEL ST 811
68638	1,240	PLASTIC ZYTEL 408
68639	1,240	PLASTIC ZYTEL 408 HS
68640	1,240	PLASTIC ZYTEL 211
68641	1,241	PLASTIC ZYTEL ST 801
68642	1,241	PLASTIC ZYTEL ST 811 HS
68643	995	PLASTIC MINLON 11C
68644	995	PLASTIC MINLON 20B
68645	995	PLASTIC MINLON 10B
68646	995	PLASTIC MINLON 12T
68647	995	PLASTIC MINLON 21C
68648	931	PLASTIC GRZ 70G13L
68649	931	PLASTIC GRZ 70G13 HS1L
68650	931	PLASTIC GRZ 70G33 HRL
68651	931	PLASTIC GRZ 71G13L
68656	931	PLASTIC GRZ 77G33L
68657	932	PLASTIC GRZ 80G33HS1L
68658	931	PLASTIC GRZ 70G33L
68659	931	PLASTIC GRZ 70G33 HS1L 70G43L
68660	931	PLASTIC GRZ 71G33L
68661	931	PLASTIC GRZ 77G43L
68662	1,115	PLASTIC RYNITE 935
68663	1,114	PLASTIC RYNITE 530
68664	1,115	PLASTIC RYNITE 555
68665	996	PLASTIC MYLAR
68666	1,137	PLASTIC TEDLAR
68667	1,137	PLASTIC TEFLON FEP 120
68668	949	PLASTIC KAPTON TYPE H
68669	949	PLASTIC KAPTON POLYIMIDE FILM
68670	1,508	VESPEL SP-22
68671	866	PLASTIC DUREZ 111
68672	866	PLASTIC DUREZ 118
68673	868	PLASTIC DUREZ 16038
68674	868	PLASTIC DUREZ 21206
68675	871	PLASTIC DUREZ 30725
68676	866	PLASTIC DUREZ 13124
68677	868	PLASTIC DUREZ 18683
68678	870	PLASTIC DUREZ 29237
68679	867	PLASTIC DUREZ 152
68680	867	PLASTIC DUREZ 156
68681	871	PLASTIC DUREZ 30959
68682	868	PLASTIC DUREZ 18441

MSFC-HDBK-527 REV F 9999942 0006769 4

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
68683	869	PLASTIC DUREZ 21372
68684	871	PLASTIC DUREZ 30698
68685	872	PLASTIC DUREZ 3948
68686	868	PLASTIC DUREZ 16378
68687	871	PLASTIC DUREZ 30417
68688	869	PLASTIC DUREZ 23410
68689	869	PLASTIC DUREZ 24337
68690	870	PLASTIC DUREZ 27962
68691	872	PLASTIC DUREZ S1-75 DAP
68692	870	PLASTIC DUREZ 24776 DAP
68693	871	PLASTIC DUREZ 31375 POLY
68694	869	PLASTIC DUREZ 23570
68695	871	PLASTIC DUREZ 3065
68696	866	PLASTIC DUREZ 115
68697	872	PLASTIC DUREZ 791
68698	868	PLASTIC DUREZ 21028
68699	869	PLASTIC DUREZ 22486
68700	866	PLASTIC DUREZ 123
68701	868	PLASTIC DUREZ 17080
68702	869	PLASTIC DUREZ 22251
68703	872	PLASTIC DUREZ 31735
68704	867	PLASTIC DUREZ 153
68705	867	PLASTIC DUREZ 157
68706	867	PLASTIC DUREZ 145
68707	869	PLASTIC DUREZ 21210
68708	870	PLASTIC DUREZ 28615
68709	868	PLASTIC DUREZ 165
68710	867	PLASTIC DUREZ 13856
68711	868	PLASTIC DUREZ 17702
68712	871	PLASTIC DUREZ 30806
68713	869	PLASTIC DUREZ 24150
68714	870	PLASTIC DUREZ 24668
68715	870	PLASTIC DUREZ 29276
68716	869	PLASTIC DUREZ 22761 DAP
68717	870	PLASTIC DUREZ 29281 DAP
68718	871	PLASTIC DUREZ 31572 POLY
68719	870	PLASTIC DUREZ 29053
68720	871	PLASTIC DUREZ 31219
68722	866	PLASTIC DUREZ 111 BLACK
68723	866	PLASTIC DUREZ 111 BROWN
68724	866	PLASTIC DUREZ 118 BLACK
68725	866	PLASTIC DUREZ 118 BROWN
68726	866	PLASTIC DUREZ 123 BLACK
68727	866	PLASTIC DUREZ 123 BROWN
68728	867	PLASTIC DUREZ 145 BLACK
68729	867	PLASTIC DUREZ 145 BROWN
68730	867	PLASTIC DUREZ 152 BLACK
68731	867	PLASTIC DUREZ 152 BROWN
68732	867	PLASTIC DUREZ 153 BLACK
68733	867	PLASTIC DUREZ 153 BROWN
68735	868	PLASTIC DUREZ 161
68737	870	PLASTIC DUREZ 265
68738	872	PLASTIC DUREZ 740
68740	868	PLASTIC DUREZ 1898
68742	866	PLASTIC DUREZ 11540

MATCD	PAGE	DESIGNATION
68744	867	PLASTIC DUREZ 13856AF
68745	867	PLASTIC DUREZ 14900
68749	868	PLASTIC DUREZ 17156
68750	868	PLASTIC DUREZ 18420
68754	868	PLASTIC DUREZ 21206 BLACK
68755	869	PLASTIC DUREZ 21206 BROWN
68758	869	PLASTIC DUREZ 22257 BLACK
68759	869	PLASTIC DUREZ 22257 BROWN
68761	869	PLASTIC DUREZ 22787
68763	869	PLASTIC DUREZ 24060
68767	870	PLASTIC DUREZ 24776 GREEN
68768	870	PLASTIC DUREZ 24776 GRAY
68769	870	PLASTIC DUREZ 27398
68773	870	PLASTIC DUREZ 29502
68774	871	PLASTIC DUREZ 30169
68775	871	PLASTIC DUREZ 30270
68776	871	PLASTIC DUREZ 30614 BLACK
68777	871	PLASTIC DUREZ 30614 GREEN
68778	871	PLASTIC DUREZ 30645
68779	896	PLASTIC EPSL186
68780	896	PLASTIC EPSL142
68781	896	PLASTIC EPSLE114-1
68782	896	PLASTIC EPSL218-1
68783	896	PLASTIC EPSL213
68784	896	PLASTIC EPSG154
68785	893	PLASTIC EPBGC184
68786	897	PLASTIC EPSLE211
68787	896	PLASTIC EPSLE174
68788	896	PLASTIC EPSL208
68789	893	PLASTIC EPBLE70-12
68790	1,077	PLASTIC PP3152A
68791	1,077	PLASTIC PP3154A
68792	1,077	PLASTIC PP4152A
68793	1,077	PLASTIC PP41E4
68794	1,077	PLASTIC PP41J7A
68795	1,075	PLASTIC PP11C8A
68796	1,074	PLASTIC PP11B12A
68797	1,075	PLASTIC PP11S20U
68798	1,074	PLASTIC PP11B30V
68799	1,077	PLASTIC PP23M2CS219
68800	1,078	PLASTIC PP4453A
68801	1,075	PLASTIC PP13R9A
68802	1,075	PLASTIC PP13T10A
68803	1,075	PLASTIC PP14C5A
68804	1,075	PLASTIC PP1454A
68805	1,075	PLASTIC PP1456A
68806	1,076	PLASTIC PP1753A
68807	1,076	PLASTIC PP1756A
68808	1,076	PLASTIC PP17C20A
68809	1,076	PLASTIC PP1852A
68810	1,076	PLASTIC PP1856A
68811	1,076	PLASTIC PP2352A
68812	1,076	PLASTIC PP23B2A
68813	1,077	PLASTIC PP23T2A
68814	1,032	PLASTIC PE101

MSFC-HDBK-527 REV F 9999942 0006770 0

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
68815	1,032	PLASTIC PE111
68816	1,030	PLASTIC PE 122
68817	1,077	PLASTIC PP3153A
68818	1,077	PLASTIC PP31530V
68819	1,077	PLASTIC PP41E2
68820	1,077	PLASTIC PP4154A
68821	1,074	PLASTIC PP1154A
68822	1,074	PLASTIC PP11512A
68823	1,075	PLASTIC PP11N12A
68824	1,074	PLASTIC PP11530V
68825	1,023	PLASTIC P1185A
68826	1,077	PLASTIC PP43J4A
68827	1,075	PLASTIC PP13N5A
68828	1,075	PLASTIC PP13510A
68829	1,075	PLASTIC PP14B12A
68830	1,075	PLASTIC PP1452A
68831	1,075	PLASTIC PP1455A
68832	1,075	PLASTIC PP1752A
68833	1,076	PLASTIC PP1754A
68834	1,076	PLASTIC PP17C6A
68835	1,076	PLASTIC PP17C20A (XO-70/XO-76)
68836	1,076	PLASTIC PP1853A
68837	1,076	PLASTIC PP2352
68838	1,076	PLASTIC PP23B2
68839	1,077	PLASTIC PP23M2
68840	1,077	PLASTIC PP24T2A
68841	1,029	PLASTIC PE 109
68842	1,030	PLASTIC PE 121
68843	1,030	PLASTIC PE 125
68844	1,032	PLASTIC PE 256
68845	1,029	PLASTIC PE 103
68846	1,029	PLASTIC PE 108
68847	1,031	PLASTIC PE 172
68848	1,031	PLASTIC PE 200
68849	1,031	PLASTIC PE 204
68850	1,031	PLASTIC PE 204C5239
68851	1,032	PLASTIC PE 216
68852	1,029	PLASTIC PE 119
68853	1,030	PLASTIC PE 127
68854	1,030	PLASTIC PE 143
68855	1,031	PLASTIC PE 179
68856	1,029	PLASTIC PE 107
68857	1,032	PLASTIC PE 220
68858	1,029	PLASTIC PE 102
68859	1,032	PLASTIC PE106
68860	1,031	PLASTIC PE 171
68861	1,031	PLASTIC PE 181
68862	1,031	PLASTIC PE 202
68863	1,031	PLASTIC PE 204C595
68864	1,031	PLASTIC PE 211
68865	1,029	PLASTIC PE 118
68866	1,030	PLASTIC PE 126
68867	1,030	PLASTIC PE 128
68868	1,031	PLASTIC PE 178
68869	1,031	PLASTIC PE 207
68870	1,030	PLASTIC PE 142
68871	1,235	PLASTIC XO-712
68872	1,236	PLASTIC XO-754
68873	1,236	PLASTIC XO-719
68874	1,043	PLASTIC PLASTOLEIN 9050
68875	1,043	PLASTIC PLASTOLEIN 9058
68876	1,044	PLASTIC PLASTOLEIN 9065
68877	1,044	PLASTIC PLASTOLEIN 907
68878	1,044	PLASTIC PLASTOLEIN 9404
68879	1,044	PLASTIC PLASTOLEIN 9091
68880	1,044	PLASTIC PLASTOLEIN 9250
68881	1,044	PLASTIC PLASTOLEIN 9215
68882	1,044	PLASTIC PLASTOLEIN 9232
68883	1,044	PLASTIC PLASTOLEIN 9717
68884	1,044	PLASTIC PLASTOLEIN 9720
68885	1,044	PLASTIC PLASTOLEIN 9731
68886	1,044	PLASTIC PLASTOLEIN 9752
68887	1,044	PLASTIC PLASTOLEIN 9756
68888	1,044	PLASTIC PLASTOLEIN 9761
68889	1,044	PLASTIC PLASTOLEIN 9762
68890	1,045	PLASTIC PLASTOLEIN 9765
68891	1,045	PLASTIC PLASTOLEIN 9776
68892	1,045	PLASTIC PLASTOLEIN 9783
68893	1,045	PLASTIC PLASTOLEIN 9789
68894	1,045	PLASTIC PLASTOLEIN 9790
68895	954	PLASTIC LD700
68896	953	PLASTIC LA701
68897	953	PLASTIC LA702
68898	953	PLASTIC LA703
68899	953	PLASTIC LD100
68900	952	PLASTIC LA104
68901	952	PLASTIC LA105
68902	952	PLASTIC LA117
68903	953	PLASTIC LA129
68904	953	PLASTIC LA302
68905	953	PLASTIC LA305
68906	953	PLASTIC LA306
68907	953	PLASTIC LA307
68908	953	PLASTIC LA308
68909	953	PLASTIC LA309
68910	952	PLASTIC LA102
68911	952	PLASTIC LA106
68912	952	PLASTIC LA113
68913	953	PLASTIC LA130
68914	952	PLASTIC LA103
68915	953	PLASTIC LA122
68916	953	PLASTIC LA124
68917	1,236	PLASTIC XQ-32
68918	1,236	PLASTIC XQ-36
68919	1,236	PLASTIC XQ-43
68920	1,236	PLASTIC XQ-46
68921	900	PLASTIC ESCORENE 1012
68922	901	PLASTIC ESCORENE 1063
68923	900	PLASTIC ESCORENE 1024
68924	901	PLASTIC ESCORENE 1074

MSFC-HDBK-527 REV F 9999942 0006771 2

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
68925	901	PLASTIC ESCORENE 1042
68926	901	PLASTIC ESCORENE 1052
68927	900	PLASTIC ESCORENE 1032
68928	901	PLASTIC ESCORENE 1172
68929	901	PLASTIC ESCORENE 1154
68930	901	PLASTIC ESCORENE 1164
68931	901	PLASTIC ESCORENE 1105
68932	901	PLASTIC ESCORENE 1222F
68933	901	PLASTIC ESCORENE 1403F
68934	901	PLASTIC ESCORENE 1224F
68935	901	PLASTIC ESCORENE 1404F
68936	903	PLASTIC ESCORENE 4152
68937	903	PLASTIC ESCORENE 4162
68938	903	PLASTIC ESCORENE 4092
68939	902	PLASTIC ESCORENE 4062
68940	902	PLASTIC ESCORENE 4082
68941	902	PLASTIC ESCORENE 4023
68942	903	PLASTIC ESCORENE 4193
68943	902	PLASTIC ESCORENE 4033
68944	903	PLASTIC ESCORENE 4103
68945	903	PLASTIC ESCORENE 4134
68946	901	PLASTIC ESCORENE 2072
68947	902	PLASTIC ESCORENE 2082
68948	902	PLASTIC ESCORENE 2092
68949	902	PLASTIC ESCORENE 3014
68950	902	PLASTIC ESCORENE 3274
68951	902	PLASTIC ESCORENE 3035
68952	902	PLASTIC ESCORENE 3235
68953	902	PLASTIC ESCORENE 3045
68954	902	PLASTIC ESCORENE 3125
68955	902	PLASTIC ESCORENE 3145
68956	903	PLASTIC ESCORENE 5181
68957	903	PLASTIC ESCORENE 5052
68958	903	PLASTIC ESCORENE 5022
68959	904	PLASTIC ESCORENE 9032
68960	904	PLASTIC ESCORENE 9022
68961	904	PLASTIC ESCORENE 9012
68962	904	PLASTIC ESCORENE 9044
68963	904	PLASTIC ESCORENE 8051
68964	904	PLASTIC ESCORENE 8032
68965	904	PLASTIC ESCORENE 8042
68966	903	PLASTIC ESCORENE 7032
68967	903	PLASTIC ESCORENE 7022
68968	903	PLASTIC ESCORENE 7033
68969	904	PLASTIC ESCORENE 7034
68970	1,138	PLASTIC TENITE ACETATE FORMULA 007 H4
68971	1,138	PLASTIC TENITE ACETATE FORMULA 007 H3
68972	1,138	PLASTIC TENITE ACETATE FORMULA 007 H2
68973	1,138	PLASTIC TENITE ACETATE FORMULA 007 H
68974	1,139	PLASTIC TENITE ACETATE FORMULA 007 MH
68975	1,138	PLASTIC TENITE ACETATE FORMULA 007 M
68976	1,139	PLASTIC TENITE ACETATE FORMULA 007 MS
68977	1,139	PLASTIC TENITE ACETATE FORMULA 007 S
68978	1,139	PLASTIC TENITE ACETATE FORMULA 036 H4
68979	1,139	PLASTIC TENITE ACETATE FORMULA 036 H3
68980	1,139	PLASTIC TENITE ACETATE FORMULA 036 H2
68981	1,139	PLASTIC TENITE ACETATE FORMULA 036 H
68982	1,139	PLASTIC TENITE ACETATE FORMULA 036 M4
68983	1,139	PLASTIC TENITE ACETATE FORMULA 036 M
68984	1,139	PLASTIC TENITE ACETATE FORMULA 036 MS
68985	1,139	PLASTIC TENITE ACETATE FORMULA 042 H4
68986	1,139	PLASTIC TENITE ACETATE FORMULA 042 H3
68987	1,139	PLASTIC TENITE ACETATE FORMULA 042 H2
68988	1,139	PLASTIC TENITE ACETATE FORMULA 042 H
68989	1,140	PLASTIC TENITE ACETATE FORMULA 042 MH
68990	1,140	PLASTIC TENITE ACETATE FORMULA 042 M
68991	1,140	PLASTIC TENITE ACETATE FORMULA 042 MS
68992	1,140	PLASTIC TENITE ACETATE FORMULA 042 S2
68993		DELETED SEE 68992
68994	1,140	PLASTIC TENITE ACETATE FORMULA 043 H4
68995	1,140	PLASTIC TENITE ACETATE FORMULA 043 H3
68996	1,140	PLASTIC TENITE ACETATE FORMULA 043 H2
68997	1,140	PLASTIC TENITE ACETATE FORMULA 043 H
68998	1,140	PLASTIC TENITE ACETATE FORMULA 043 MH
68999	1,140	PLASTIC TENITE ACETATE FORMULA 043 M
69000	1,140	PLASTIC TENITE ACETATE FORMULA 043 MS
69001	1,140	PLASTIC TENITE ACETATE FORMULA 043 S
69002	1,140	PLASTIC TENITE ACETATE FORMULA 043 S2
69003	1,141	PLASTIC TENITE ACETATE FORMULA 054 H4
69004	1,141	PLASTIC TENITE ACETATE FORMULA 054 H3
69005	1,141	PLASTIC TENITE ACETATE FORMULA 054 H2
69006	1,140	PLASTIC TENITE ACETATE FORMULA 054 H
69007	1,141	PLASTIC TENITE ACETATE FORMULA 054 M4
69008	1,141	PLASTIC TENITE ACETATE FORMULA 054 M
69009	1,141	PLASTIC TENITE ACETATE FORMULA 054 MS
69010	1,141	PLASTIC TENITE ACETATE FORMULA 054 S
69011	1,141	PLASTIC TENITE ACETATE FORMULA 100 H4
69012	1,141	PLASTIC TENITE ACETATE FORMULA 100 H3
69013	1,141	PLASTIC TENITE ACETATE FORMULA 100 H2
69014	1,141	PLASTIC TENITE ACETATE FORMULA 100 H
69015	1,141	PLASTIC TENITE ACETATE FORMULA 100 MH
69016	1,141	PLASTIC TENITE ACETATE FORMULA 100 M
69017	1,141	PLASTIC TENITE ACETATE FORMULA 100 MS
69018	1,142	PLASTIC TENITE ACETATE FORMULA 103 H4
69019	1,142	PLASTIC TENITE ACETATE FORMULA 103 H3
69020	1,142	PLASTIC TENITE ACETATE FORMULA 103 H2
69021	1,142	PLASTIC TENITE ACETATE FORMULA 103 H
69022	1,142	PLASTIC TENITE ACETATE FORMULA 103 MH
69023	1,142	PLASTIC TENITE ACETATE FORMULA 103 M
69024	1,142	PLASTIC TENITE ACETATE FORMULA 103 MS
69025	1,142	PLASTIC TENITE ACETATE FORMULA 104 H3
69026	1,142	PLASTIC TENITE ACETATE FORMULA 104 H2
69027	1,142	PLASTIC TENITE ACETATE FORMULA 104 H
69028	1,142	PLASTIC TENITE BUTYRATE FORMULA 203 H4
69029	1,142	PLASTIC TENITE BUTYRATE FORMULA 203 H3
69030	1,142	PLASTIC TENITE BUTYRATE FORMULA 203 H2
69031	1,142	PLASTIC TENITE BUTYRATE FORMULA 203 H
69032	1,143	PLASTIC TENITE BUTYRATE FORMULA 203 MH
69033	1,143	PLASTIC TENITE BUTYRATE FORMULA 203 M
69034	1,143	PLASTIC TENITE BUTYRATE FORMULA 203 MS

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
69035	1,143	PLASTIC TENITE BUTYRATE FORMULA 203 S
69036	1,143	PLASTIC TENITE BUTYRATE FORMULA 203 S2
69037	1,143	PLASTIC TENITE BUTYRATE FORMULA 205 H4
69038	1,143	PLASTIC TENITE BUTYRATE FORMULA 205 H3
69039	1,143	PLASTIC TENITE BUTYRATE FORMULA 205 H2
69040	1,143	PLASTIC TENITE BUTYRATE FORMULA 205 H
69041	1,143	PLASTIC TENITE BUTYRATE FORMULA 205 M4
69042	1,143	PLASTIC TENITE BUTYRATE FORMULA 205 M
69043	1,143	PLASTIC TENITE BUTYRATE FORMULA 205 MS
69044	1,143	PLASTIC TENITE BUTYRATE FORMULA 205 S
69045	1,143	PLASTIC TENITE BUTYRATE FORMULA 205 S2
69046	1,144	PLASTIC TENITE BUTYRATE FORMULA 217 H4
69047	1,144	PLASTIC TENITE BUTYRATE FORMULA 217 H3
69048	1,144	PLASTIC TENITE BUTYRATE FORMULA 217 H2
69049	1,144	PLASTIC TENITE BUTYRATE FORMULA 217 H
69050	1,150	PLASTIC TENITE POLYETHYLENE E6838-913P
69051	1,150	PLASTIC TENITE POLYETHYLENE E6838-868F
69052	1,150	PLASTIC TENITE POLYETHYLENE E6838-914P
69053	1,149	PLASTIC TENITE POLYETHYLENE E6838-807F
69054	1,149	PLASTIC TENITE POLYETHYLENE E6838-793F
69055	1,144	PLASTIC TENITE BUTYRATE FORMULA 217 MH
69056	1,144	PLASTIC TENITE BUTYRATE FORMULA 217 M
69057	1,144	PLASTIC TENITE BUTYRATE FORMULA 217 MS
69058	1,144	PLASTIC TENITE BUTYRATE FORMULA 217 S
69059	1,144	PLASTIC TENITE BUTYRATE FORMULA 217 S2
69060	1,144	PLASTIC TENITE BUTYRATE FORMULA 236 H4
69061	1,144	PLASTIC TENITE BUTYRATE FORMULA 236 H3
69062	1,144	PLASTIC TENITE BUTYRATE FORMULA 236 H2
69063	1,144	PLASTIC TENITE BUTYRATE FORMULA 236 H
69064	1,144	PLASTIC TENITE BUTYRATE FORMULA 236 MH
69065	1,145	PLASTIC TENITE BUTYRATE FORMULA 236-M
69066	1,145	PLASTIC TENITE BUTYRATE FORMULA 236 MS
69067	1,145	PLASTIC TENITE BUTYRATE FORMULA 236 S
69068	1,145	PLASTIC TENITE BUTYRATE FORMULA 264 H4
69069	1,145	PLASTIC TENITE BUTYRATE FORMULA 264 H3
69070	1,145	PLASTIC TENITE BUTYRATE FORMULA 264 H2
69071	1,145	PLASTIC TENITE BUTYRATE FORMULA 264 H
69072	1,145	PLASTIC TENITE BUTYRATE FORMULA 264 M4
69073	1,145	PLASTIC TENITE BUTYRATE FORMULA 264 M
69074	1,145	PLASTIC TENITE BUTYRATE FORMULA 264 MS
69075	1,145	PLASTIC TENITE BUTYRATE FORMULA 264 S
69076	1,145	PLASTIC TENITE BUTYRATE FORMULA 264 S2
69077	1,146	PLASTIC TENITE BUTYRATE FORMULA 479 H4
69078	1,146	PLASTIC TENITE BUTYRATE FORMULA 479 H3
69079	1,145	PLASTIC TENITE BUTYRATE FORMULA 479 H2
69080	1,145	PLASTIC TENITE BUTYRATE FORMULA 479 H
69081	1,146	PLASTIC TENITE BUTYRATE FORMULA 479 MH
69082	1,146	PLASTIC TENITE BUTYRATE FORMULA 479 M
69083	1,146	PLASTIC TENITE BUTYRATE FORMULA 479 MS
69084	1,146	PLASTIC TENITE BUTYRATE FORMULA 525 H4
69085	1,146	PLASTIC TENITE BUTYRATE FORMULA 525 H3
69086	1,146	PLASTIC TENITE BUTYRATE FORMULA 525 H2
69087	1,146	PLASTIC TENITE BUTYRATE FORMULA 525 H
69088	1,146	PLASTIC TENITE BUTYRATE FORMULA 525 M4
69089	1,146	PLASTIC TENITE BUTYRATE FORMULA 525 M
69090	1,146	PLASTIC TENITE BUTYRATE FORMULA 525 MS
69091	1,146	PLASTIC TENITE BUTYRATE FORMULA 525 S
69092	1,146	PLASTIC TENITE BUTYRATE FORMULA 525 S2
69093	1,147	PLASTIC TENITE BUTYRATE FORMULA 554 H4
69094	1,147	PLASTIC TENITE BUTYRATE FORMULA 554 H3
69095	1,147	PLASTIC TENITE BUTYRATE FORMULA 554 H2
69096	1,147	PLASTIC TENITE BUTYRATE FORMULA 554 H
69097	1,147	PLASTIC TENITE BUTYRATE FORMULA 554 MH
69098	1,147	PLASTIC TENITE BUTYRATE FORMULA 554 M
69099	1,147	PLASTIC TENITE BUTYRATE FORMULA 554 MS
69100	1,147	PLASTIC TENITE BUTYRATE FORMULA 554 S
69101	1,147	PLASTIC TENITE BUTYRATE FORMULA 554 S2
69102	1,154	PLASTIC TENITE PROPIONATE FORMULA 306 H6
69103	1,154	PLASTIC TENITE PROPIONATE FORMULA 306 H5
69104	1,154	PLASTIC TENITE PROPIONATE FORMULA 306 H4
69105	1,154	PLASTIC TENITE PROPIONATE FORMULA 306 H3
69106	1,154	PLASTIC TENITE PROPIONATE FORMULA 306 H2
69107	1,153	PLASTIC TENITE PROPIONATE FORMULA 306 H
69108	1,154	PLASTIC TENITE PROPIONATE FORMULA 306 MH
69109	1,154	PLASTIC TENITE PROPIONATE FORMULA 309 H6
69110	1,154	PLASTIC TENITE PROPIONATE FORMULA 309 H5
69111	1,154	PLASTIC TENITE PROPIONATE FORMULA 309 H4
69112	1,154	PLASTIC TENITE PROPIONATE FORMULA 309 H3
69113	1,154	PLASTIC TENITE PROPIONATE FORMULA 309 H2
69114	1,155	PLASTIC TENITE PROPIONATE FORMULA 311 H6
69115	1,155	PLASTIC TENITE PROPIONATE FORMULA 311 H5
69116	1,154	PLASTIC TENITE PROPIONATE FORMULA 311 H4
69117	1,154	PLASTIC TENITE PROPIONATE FORMULA 311 H3
69118	1,154	PLASTIC TENITE PROPIONATE FORMULA 311 H2
69119	1,155	PLASTIC TENITE PROPIONATE FORMULA 319 H6
69120	1,155	PLASTIC TENITE PROPIONATE FORMULA 319 H5
69121	1,155	PLASTIC TENITE PROPIONATE FORMULA 319 H4
69122	1,155	PLASTIC TENITE PROPIONATE FORMULA 319 H3
69123	1,155	PLASTIC TENITE PROPIONATE FORMULA 319 H2
69124	1,155	PLASTIC TENITE PROPIONATE FORMULA 325 H6
69125	1,155	PLASTIC TENITE PROPIONATE FORMULA 325 H5
69126	1,155	PLASTIC TENITE PROPIONATE FORMULA 325 H4
69127	1,155	PLASTIC TENITE PROPIONATE FORMULA 325 H3
69128	1,155	PLASTIC TENITE PROPIONATE FORMULA 325 H2
69129	1,155	PLASTIC TENITE PROPIONATE FORMULA 325 H
69130	1,155	PLASTIC TENITE PROPIONATE FORMULA 325 MH
69131	1,156	PLASTIC TENITE PROPIONATE FORMULA 326 H6
69132	1,156	PLASTIC TENITE PROPIONATE FORMULA 326 H5
69133	1,156	PLASTIC TENITE PROPIONATE FORMULA 326 H4
69134	1,156	PLASTIC TENITE PROPIONATE FORMULA 326 H3
69135	1,156	PLASTIC TENITE PROPIONATE FORMULA 326 H2
69136	1,156	PLASTIC TENITE PROPIONATE FORMULA 327 H6
69137	1,156	PLASTIC TENITE PROPIONATE FORMULA 327 H5
69138	1,156	PLASTIC TENITE PROPIONATE FORMULA 327 H4
69139	1,156	PLASTIC TENITE PROPIONATE FORMULA 327 H3
69140	1,156	PLASTIC TENITE PROPIONATE FORMULA 327 H2
69141	1,156	PLASTIC TENITE PROPIONATE FORMULA 327 H
69142	1,156	PLASTIC TENITE PROPIONATE FORMULA 327 MH
69143	1,158	PLASTIC TENITE PROPIONATE FORMULA 350 H6
69144	1,158	PLASTIC TENITE PROPIONATE FORMULA 350 H5

MSFC-HDBK-527 REV F 9999942 0006773 6

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
69145	1,158	PLASTIC TENITE PROPIONATE FORMULA 350 H4
69146	1,091	PLASTIC PROPIONATE FORMULA 350 H3
69147	1,157	PLASTIC TENITE PROPIONATE FORMULA 350 H2
69148	1,157	PLASTIC TENITE PROPIONATE FORMULA 333 H6
69149	1,157	PLASTIC TENITE PROPIONATE FORMULA 333 H5
69150	1,157	PLASTIC TENITE PROPIONATE FORMULA 333 H4
69151	1,157	PLASTIC TENITE PROPIONATE FORMULA 333 H3
69152	1,156	PLASTIC TENITE PROPIONATE FORMULA 333 H2
69153	1,156	PLASTIC TENITE PROPIONATE FORMULA 333 H
69154	1,157	PLASTIC TENITE PROPIONATE FORMULA 333 MH
69155	1,157	PLASTIC TENITE PROPIONATE FORMULA 333 M
69156	1,157	PLASTIC TENITE PROPIONATE FORMULA 338 H6
69157	1,157	PLASTIC TENITE PROPIONATE FORMULA 338 H5
69158	1,157	PLASTIC TENITE PROPIONATE FORMULA 338 H4
69159	1,157	PLASTIC TENITE PROPIONATE FORMULA 338 H3
69160	1,157	PLASTIC TENITE PROPIONATE FORMULA 338 H2
69161	1,157	PLASTIC TENITE PROPIONATE FORMULA 338 H
69162	1,157	PLASTIC TENITE PROPIONATE FORMULA 338 MH
69163	1,158	PLASTIC TENITE PROPIONATE FORMULA 353 H6
69164	1,158	PLASTIC TENITE PROPIONATE FORMULA 353 H5
69165	1,158	PLASTIC TENITE PROPIONATE FORMULA 353 H4
69166	1,158	PLASTIC TENITE PROPIONATE FORMULA 353 H3
69167	1,158	PLASTIC TENITE PROPIONATE FORMULA 353 H2
69168	1,158	PLASTIC TENITE PROPIONATE FORMULA 353 H
69169	1,158	PLASTIC TENITE PROPIONATE FORMULA 353 MH
69170	1,158	PLASTIC TENITE PROPIONATE FORMULA 353 M
69171	1,158	PLASTIC TENITE PROPIONATE FORMULA 353 MS
69172	1,158	PLASTIC TENITE PROPIONATE FORMULA 353 S
69173	1,158	PLASTIC TENITE PROPIONATE FORMULA 353 S2
69174	1,159	PLASTIC TENITE PROPIONATE FORMULA 354 H3
69175	1,159	PLASTIC TENITE PROPIONATE FORMULA 354 H2
69176	1,159	PLASTIC TENITE PROPIONATE FORMULA 358 H6
69177	1,159	PLASTIC TENITE PROPIONATE FORMULA 358 H5
69178	1,159	PLASTIC TENITE PROPIONATE FORMULA 358 H4
69179	1,159	PLASTIC TENITE PROPIONATE FORMULA 358 H3
69180	1,159	PLASTIC TENITE PROPIONATE FORMULA 358 H2
69181		DELETED SEE 69168
69182	1,152	PLASTIC TENITE POLYPROPYLENE 808P
69183	1,150	PLASTIC TENITE POLYPROPYLENE 1550P
69184	1,150	PLASTIC TENITE POLYPROPYLENE 1924P
69185	1,152	PLASTIC TENITE POLYPROPYLENE E8-913P
69186	1,152	PLASTIC TENITE POLYPROPYLENE E8-914P
69187	1,152	PLASTIC TENITE POLYPROPYLENE E8-849P
69188	1,152	PLASTIC TENITE POLYPROPYLENE E7-467P
69189	1,151	PLASTIC TENITE POLYPROPYLENE 4G7DP
69190	1,152	PLASTIC TENITE POLYPROPYLENE P7673-499P
69191	1,153	PLASTIC TENITE POLYPROPYLENE P7673-607P
69192	1,153	PLASTIC TENITE POLYPROPYLENE P7673-996P
69193	1,151	PLASTIC TENITE POLYPROPYLENE 4E31
69194	1,151	PLASTIC TENITE POLYPROPYLENE 4E3V
69195	1,150	PLASTIC TENITE POLYPROPYLENE 4220
69196	1,150	PLASTIC TENITE POLYPROPYLENE 4231
69197	1,150	PLASTIC TENITE POLYPROPYLENE 4230
69198	1,150	PLASTIC TENITE POLYPROPYLENE 4232
69199	1,152	PLASTIC TENITE POLYPROPYLENE H240
69200	1,151	PLASTIC TENITE POLYPROPYLENE 4242
69201	1,151	PLASTIC TENITE POLYPROPYLENE 4250
69202	1,151	PLASTIC TENITE POLYPROPYLENE 4531
69203	1,151	PLASTIC TENITE POLYPROPYLENE 4532
69204	1,151	PLASTIC TENITE POLYPROPYLENE 4K31
69205	1,151	PLASTIC TENITE POLYPROPYLENE 4K32
69206	1,152	PLASTIC TENITE POLYPROPYLENE 4L31
69207	1,152	PLASTIC TENITE POLYPROPYLENE 4P31
69208	1,152	PLASTIC TENITE POLYPROPYLENE 4P32
69209	1,151	PLASTIC TENITE POLYPROPYLENE 4E11
69210	1,153	PLASTIC TENITE POLYPROPYLENE P7673-780A
69211	1,152	PLASTIC TENITE POLYPROPYLENE P7673-469P
69212	1,153	PLASTIC TENITE POLYPROPYLENE P7673-648G
69213	1,153	PLASTIC TENITE POLYPROPYLENE P7673-940
69214	1,153	PLASTIC TENITE POLYPROPYLENE R7673-930P
69215	1,153	PLASTIC TENITE POLYPROPYLENE P7673-984
69216	1,152	PLASTIC TENITE POLYPROPYLENE 4M40
69218	913	PLASTIC FOAMABLE TENITE POLYPROPYLENE P2635-08AA
69219	950	PLASTIC KODAR PETG COPOLYSTER 6763
69220	1,147	PLASTIC TENITE POLYALLOMER 5021
69221	1,147	PLASTIC TENITE POLYALLOMER 5020
69222	1,148	PLASTIC TENITE POLYALLOMER 5151
69223	1,147	PLASTIC TENITE POLYALLOMER 512V
69224	1,149	PLASTIC TENITE POLYETHYLENE 800
69225	1,148	PLASTIC TENITE POLYETHYLENE 1550
69226	1,149	PLASTIC TENITE POLYETHYLENE 811
69227	1,148	PLASTIC TENITE POLYETHYLENE 155W
69228	1,148	PLASTIC TENITE POLYETHYLENE 1390P
69229	1,149	PLASTIC TENITE POLYETHYLENE 808
69230	1,149	PLASTIC TENITE POLYETHYLENE 1924P
69231	1,148	PLASTIC TENITE POLYETHYLENE 1811
69232	1,149	PLASTIC TENITE POLYETHYLENE 1930
69233	1,148	PLASTIC TENITE POLYETHYLENE 1810
69234	1,148	PLASTIC TENITE POLYETHYLENE 183M
69235	1,148	PLASTIC TENITE POLYETHYLENE 183H
69236	1,148	PLASTIC TENITE POLYETHYLENE 1840
69237	1,148	PLASTIC TENITE POLYETHYLENE 184L
69238	1,148	PLASTIC TENITE POLYETHYLENE 184M
69239	1,149	PLASTIC TENITE POLYETHYLENE 1870
69240	1,149	PLASTIC TENITE POLYETHYLENE 18B0
69241	1,148	PLASTIC TENITE POLYETHYLENE 1800
69242	1,148	PLASTIC TENITE POLYETHYLENE 1540F
69243	1,149	PLASTIC TENITE POLYETHYLENE 1925F
69244	1,149	PLASTIC TENITE POLYETHYLENE E6838-735
69245	1,149	PLASTIC TENITE POLYETHYLENE E6838-768F
69246	1,149	PLASTIC TENITE POLYETHYLENE E6838-781F
69247	1,149	PLASTIC TENITE POLYETHYLENE E6838-849P
69248	954	PLASTIC LEXAN 101
69249	954	PLASTIC LEXAN 141
69250	955	PLASTIC LEXAN 144
69251	954	PLASTIC LEXAN 103
69252	954	PLASTIC LEXAN 123
69253	957	PLASTIC LEXAN 920
69254	929	PLASTIC GRILAN A28GM
69255	929	PLASTIC GRILON A28NY

MSFC-HDBK-527 REV F ■ 9999942 0006774 8 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
69256	929	PLASTIC GRILON A28VO
69257	929	PLASTIC GRILON CA6E
69258	930	PLASTIC GRILON PV3H
69259	930	PLASTIC GRILON PVN154
69260	930	PLASTIC GRILON W3941
69261	929	PLASTIC GRILON A28NX
69262	929	PLASTIC GRILON A28NZ
69263	929	PLASTIC GRILON BT40
69264	929	PLASTIC GRILON CR9
69265	930	PLASTIC GRILON PVN3H
69266	930	PLASTIC GRILON R47HW
69267	930	PLASTIC GRILON W5744
69268	927	PLASTIC GRILAMID L16GM
69269	928	PLASTIC GRILAMID LV43H
69270	928	PLASTIC GRILAMID W5941
69271	928	PLASTIC GRILAMID TR55
69272	928	PLASTIC GRILAMID TR55LX
69273	928	PLASTIC GRILAMID L25W40NZ NYLON 12
69274	928	PLASTIC GRILAMID W2291 NYLON 12
69275	928	PLASTIC GRILAMID W6923
69276	928	PLASTIC GRILAMID TR55UV
69277	1,117	PLASTIC SMC
69278	863	PLASTIC DMC
69279	907	PLASTIC FILLITE 200/7
69280	907	PLASTIC FILLITE 100/7
69281	907	PLASTIC FILLITE 52/7/5
69282	907	PLASTIC FILLITE 300/7
69283	907	PLASTIC FILLITE PFA
69284	907	PLASTIC FILLITE P2000
69285	907	PLASTIC FILLITE M32
69286	907	PLASTIC FILLITE IN POLYESTER RESIN
69287	907	PLASTIC FILLITE MICRO BALLONS
69288	907	PLASTIC FILLITE MICRO BALLONS IN EPOXY RESINS
69289	908	PLASTIC FLUOROLOY C
69290	908	PLASTIC FLUOROLOY X
69291	909	PLASTIC FLUOROLOY Z
69292	908	PLASTIC FLUOROLOY A
69293	908	PLASTIC FLUOROLOY G
69294	909	PLASTIC FLUOROLOY Y
69295	908	PLASTIC FLUOROGOLD
69296	951	PLASTIC KRONITEX 50
69297	951	PLASTIC KRONITEX 1000
69298	951	PLASTIC KRONITEX TCP
69299	951	PLASTIC KRONITEX 100
69300	951	PLASTIC KRONITEX CDD
69301	951	PLASTIC KRONITEX TXP
69302	1,123	PLASTIC STYPOL 40-0042
69303	1,128	PLASTIC STYPOL 40-I029
69304	1,124	PLASTIC STYPOL 40-1103
69305	1,124	PLASTIC STYPOL 40-1124
69306	1,124	PLASTIC STYPOL 40-1602
69307	1,124	PLASTIC STYPOL 40-0087
69308	1,124	PLASTIC STYPOL 40-2057
69309	1,124	PLASTIC STYPOL 40-0048
69310	1,124	PLASTIC STYPOL 40-1037
69311	1,124	PLASTIC STYPOL 40-1117
69312	1,124	PLASTIC STYPOL 40-1507
69313	1,124	PLASTIC STYPOL 40-1603
69314	1,124	PLASTIC STYPOL 40-2025
69315	1,124	PLASTIC STYPOL 40-2026
69316		DELETED SEE 69308
69317	1,125	PLASTIC STYPOL 40-2092
69318	1,125	PLASTIC STYPOL 40-2353
69319	1,125	PLASTIC STYPOL 40-2405
69320	1,125	PLASTIC STYPOL 40-2465
69321	1,125	PLASTIC STYPOL 40-27II
69322	1,125	PLASTIC STYPOL 40-2782
69323	1,125	PLASTIC STYPOL 40-2988
69324	1,126	PLASTIC STYPOL 40-2990
69325	1,126	PLASTIC STYPOL 40-3303
69326	1,126	PLASTIC STYPOL 40-3904
69327	1,126	PLASTIC STYPOL 40-3909
69328	1,126	PLASTIC STYPOL 40-3929
69329	1,126	PLASTIC STYPOL 40-3941
69330	1,127	PLASTIC STYPOL 40-4901
69331	1,127	PLASTIC STYPOL 40-4920
69332	1,127	PLASTIC STYPOL 40-6519
69333	1,127	PLASTIC STYPOL 40-7052
69334	1,127	PLASTIC STYPOL 40-7119
69335	1,127	PLASTIC STYPOL 40-7134
69336	1,128	PLASTIC STYPOL 40-7263
69337	1,128	PLASTIC STYPOL 40-8408
69338	1,128	PLASTIC STYPOL 40-9311
69339	1,124	PLASTIC STYPOL 40-2072
69340	1,125	PLASTIC STYPOL 40-2304
69341	1,125	PLASTIC STYPOL 40-2364
69342	1,125	PLASTIC STYPOL 40-2448
69343	1,125	PLASTIC STYPOL 40-2584
69344	1,125	PLASTIC STYPOL 40-2580
69345	1,125	PLASTIC STYPOL 40-2974
69346	1,126	PLASTIC STYPOL 40-2989
69347	1,126	PLASTIC STYPOL 40-3267
69348	1,126	PLASTIC STYPOL 40-3323
69349	1,126	PLASTIC STYPOL 40-3906
69350	1,126	PLASTIC STYPOL 40-3925
69351	1,126	PLASTIC STYPOL 40-3939
69352	1,127	PLASTIC STYPOL 40-3950
69353	1,127	PLASTIC STYPOL 40-4902
69354	1,127	PLASTIC STYPOL 40-5013
69355	1,127	PLASTIC STYPOL 40-7001
69356	1,127	PLASTIC STYPOL 40-7114
69357	1,127	PLASTIC STYPOL 40-7131
69358	1,127	PLASTIC STYPOL 40-7193
69359	1,128	PLASTIC STYPOL 40-8003
69360	1,128	PLASTIC STYPOL 40-9303
69361	1,128	PLASTIC STYPOL 40-9518
69362	1,123	PLASTIC STYPOL 40-0008
69363	811	PLASTIC ACPOL 42-2673
69364	811	PLASTIC ACPOL 42-2640
69365	811	PLASTIC ACPOL 42-2675

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006775 T

MATCD	PAGE	DESIGNATION
69366	1,009	PLASTIC NUPOL 46-4001
69367	1,009	PLASTIC NUPOL 46-4004
69368	1,009	PLASTIC NUPOL 46-4003
69369	1,009	PLASTIC NUPOL 46-4008
69370	1,009	PLASTIC NUPOL 46-4013
69371	1,009	PLASTIC NUPOL 46-4076
69372	1,010	PLASTIC NUPOL 46-4400
69373	1,010	PLASTIC NUPOL 46-4435
69374	1,010	PLASTIC NUPOL 46-8000
69375	1,010	PLASTIC NUPOL 46-8016
69376	1,009	PLASTIC NUPOL 46-4020
69377	1,009	PLASTIC NUPOL 46-4250
69378	1,010	PLASTIC NUPOL 46-4421
69379	1,010	PLASTIC NUPOL 46-4440
69380	803	PLASTIC 46-8012
69381	1,128	PLASTIC STYPOL 70-0001
69382	1,128	PLASTIC STYPOL 72-5038
69383	1,128	PLASTIC STYPOL 80-1126
69384	1,128	PLASTIC STYPOL 80-3297
69385	1,129	PLASTIC STYPOL 83-2030
69386	1,129	PLASTIC STYPOL 83-2105
69387	1,129	PLASTIC STYPOL 83-2140
69388	1,128	PLASTIC STYPOL 70-0004
69389	1,129	PLASTIC STYPOL 80-II20
69390	1,129	PLASTIC STYPOL 80-II27
69391	1,129	PLASTIC STYPOL 83-2000
69392	1,129	PLASTIC STYPOL 83-2035
69393	1,129	PLASTIC STYPOL 83-2139
69394	1,124	PLASTIC STYPOL 40-1021
69395	946	PLASTIC INTERPOL 047-1050
69396	922	PLASTIC FREEFLO 49-0301
69397	957	PLASTIC LEXAN 950
69398	955	PLASTIC LEXAN 191
69399	956	PLASTIC LEXAN 3412 20% GLASS
69400	956	PLASTIC LEXAN 3414 40% GLASS
69401	954	PLASTIC LEXAN 121
69402	954	PLASTIC LEXAN 104
69403	954	PLASTIC LEXAN 124
69404	955	PLASTIC LEXAN 193
69405	956	PLASTIC LEXAN 303
69406	957	PLASTIC LEXAN 920A
69407	957	PLASTIC LEXAN 940A
69408	957	PLASTIC LEXAN 950A
69409	956	PLASTIC LEXAN 500 10% GLASS
69410	956	PLASTIC LEXAN 3413 30% GLASS
69411	1,235	PLASTIC XENOY 5220
69412	1,235	PLASTIC XENOY 2230
69413	1,235	PLASTIC XENOY 3220
69414	1,235	PLASTIC XENOY 3221
69415	1,235	PLASTIC XENOY 6120
69416	1,235	PLASTIC XENOY 6123
69417	1,235	PLASTIC XENOY 6240 10% GLASS
69418	1,235	PLASTIC XENOY 6380 30% GLASS
69419	1,235	PLASTIC XENOY 3225
69420	1,235	PLASTIC XENOY 6121

MATCD	PAGE	DESIGNATION
69421	1,235	PLASTIC XENOY 6620
69422	1,235	PLASTIC XENOY 6370 30% GLASS
69423	1,006	PLASTIC NORYL SE 100
69424	1,004	PLASTIC NORYL HS1000
69425	1,003	PLASTIC NORYL 731
69426	1,005	PLASTIC NORYL N300
69427	1,004	PLASTIC NORYL GFN3
69428	1,006	PLASTIC NORYL PX0722
69429	1,006	PLASTIC NORYL PX1222
69430	1,006	PLASTIC NORYL PX1265
69431	1,006	PLASTIC NORYL PX1391
69432	1,005	PLASTIC NORYL PC180
69433	1,006	PLASTIC NORYL UV180
69434	1,005	PLASTIC NORYL N190
69435	1,005	PLASTIC NORYL N225
69436	1,004	PLASTIC NORYL HS2000
69437	1,004	PLASTIC NORYL GFN2
69438	1,006	PLASTIC NORYL SE1-CFN2
69439	1,006	PLASTIC NORYL PN235
69440	1,006	PLASTIC NORYL PX844
69441	1,006	PLASTIC NORYL PX888
69442	1,006	PLASTIC NORYL PX1390
69443	1,004	PLASTIC NORYL HB235
69444	1,004	PLASTIC NORYL CRT200
69445	963	PLASTIC LOMOD B0100
69446	963	PLASTIC LOMOD B0200
69447	964	PLASTIC LOMOD B0250
69448	964	PLASTIC LOMOD B0800
69449	964	PLASTIC LOMOD R0520
69450	964	PLASTIC LOMOD B0220
69451	963	PLASTIC LOMOD B0150
69452	964	PLASTIC LOMOD B0852
69453	1,193	PLASTIC ULTEM 1010
69455	1,193	PLASTIC ULTEM 2400
69456	1,193	PLASTIC ULTEM 6100
69457	1,193	PLASTIC ULTEM 6202
69458	1,193	PLASTIC ULTEM 4001
69462	1,193	PLASTIC ULTEM 6000
69463	1,193	PLASTIC ULTEM 6200
69464	1,193	PLASTIC ULTEM 4000
69465	1,222	PLASTIC VALOX 325
69466	1,222	PLASTIC VALOX 365
69467	1,223	PLASTIC VALOX DR-48 15% GLASS
69468	1,222	PLASTIC VALOX 414 40% GLASS
69469	1,222	PLASTIC VALOX 553 30% GLASS
69470	1,222	PLASTIC VALOX 701 35% GLASS
69471	1,223	PLASTIC VALOX 752 45% GLASS
69472	1,223	PLASTIC VALOX 780 40% GLASS
69473	1,223	PLASTIC VALOX 830 30% GLASS
69474	1,223	PLASTIC VALOX 855 15% GLASS
69475	1,224	PLASTIC VALOX DR-51 15% GLASS
69476	1,222	PLASTIC VALOX 420 30% GLASS
69477	1,222	PLASTIC VALOX 430 30% GLASS
69478	1,222	PLASTIC VALOX 508 30% GLASS
69479	1,223	PLASTIC VALOX 735 40% GLASS

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006776 1 ■

MATCD	PAGE	DESIGNATION
69480	1,223	PLASTIC VALOX 815 15% GLASS
69481	1,223	PLASTIC VALOX 850 15% GLASS
69482	1,223	PLASTIC VALOX 865 30% GLASS
69483	1,223	PLASTIC VALOX 740 30% MINERAL
69484	1,223	PLASTIC VALOX 760 25% MINERAL
69485	842	PLASTIC CLEARSTUF 5901
69486	842	PLASTIC CLEARSTUF 7202
69487	842	PLASTIC CLEARSTUF 7204
69488	842	PLASTIC CLEARSTUF 7207
69489	842	PLASTIC CLEARSTUF 8006
69490	842	PLASTIC CLEARSTUF 8403
69491	842	PLASTIC CLEARSTUF 9504
69492	842	PLASTIC CLEARSTUF 9506
69493	842	PLASTIC CLEARSTUF 1006
69494	1,226	PLASTIC VITUF 6204
69495	1,226	PLASTIC VITUF 6209
69496	1,226	PLASTIC VITUF 7002
69497	1,227	PLASTIC VITUF 7800G
69498	1,227	PLASTIC VITUF 9505
69500	1,031	PLASTIC PE 207F
69501	1,032	PLASTIC PE 307TS
69502	1,227	PLASTIC VPE-4583A
69503	1,029	PLASTIC PE 100
69505	1,031	PLASTIC PE 2000
69506	1,032	PLASTIC PE 222
69507	1,227	PLASTIC VPE-4670A
69508	1,228	PLASTIC VPE5066A
69509	1,227	PLASTIC VPE-5253
69510	1,227	PLASTIC VPE-5833A
69511	1,228	PLASTIC VPE-5987A
69512	951	PLASTIC KYNAR
69513	952	PLASTIC KYNAR PVDF
69514	859	PLASTIC DERAKANE 470
69515	859	PLASTIC DERAKANE 510N
69516	1,051	PLASTIC PLEXIGLASS G AND 2 UVA
69517	1,051	PLASTIC PLEXIGLASS K
69518		DELETED SEE 00298
69519	913	PLASTIC FOAMEX
69520		DELETED SEE 68564
69521	852	PLASTIC CPVC TYPE 4
69522	1,093	PLASTIC PVC TYPE I
69523	990	PLASTIC MICARTA 51
69524	990	PLASTIC MICARTA 5A2
69525	991	PLASTIC MICARTA 5A3
69526	994	PLASTIC MICARTA HY290-2
69527	989	PLASTIC MICARTA 20005
69528	991	PLASTIC MICARTA 76 5A1
69529	991	PLASTIC MICARTA 79
69530	991	PLASTIC MICARTA 91
69531	991	PLASTIC MICARTA 97
69532	993	PLASTIC MICARTA HY1928
69533	989	PLASTIC MICARTA 20007
69534	993	PLASTIC MICARTA HY1755
69535	993	PLASTIC MICARTA HY2180
69536	993	PLASTIC MICARTA HY2140
69537	993	PLASTIC MICARTA HY2055
69538	991	PLASTIC MICARTA 5A4
69539	993	PLASTIC MICARTA HY180
69540	993	PLASTIC MICARTA HY180-1
69541	994	PLASTIC MICARTA HY278
69542	994	PLASTIC MICARTA HY512
69543	994	PLASTIC MICARTA HY689
69544	993	PLASTIC MICARTA HY1216
69545	993	PLASTIC MICARTA HY1293
69546	993	PLASTIC MICARTA HY1806
69547	994	PLASTIC MICARTA HY964
69548	993	PLASTIC MICARTA HY1384
69549	993	PLASTIC MICARTA HY1457
69550	993	PLASTIC MICARTA HY1527
69551	993	PLASTIC MICARTA HY1828
69552	1,018	PLASTIC NYLON 101
69553	985	PLASTIC MC901
69554	1,017	PLASTIC NYLATRON GSM
69555	1,193	PLASTIC ULTRA-WEAR UHMPE
69556	1,061	PLASTIC POLYPENCE TFE
69558	996	PLASTIC MONOCAST
69559	1,062	PLASTIC POLYPENCO TR-1
69560	908	PLASTIC FLOUROSINT TFE
69561	908	PLASTIC FLOUROSINT 500
69562	908	PLASTIC FLOUROSINT 207
69563	852	PLASTIC CROSSLINKED POLYSTYRENE Q2005
69564		DELETED SEE 68558
69565	838	PLASTIC CAST ACRYLIC
69566	1,017	PLASTIC NYLAFLOW
69567	1,133	PLASTIC SUPERFLEX FR-1
69568	1,133	PLASTIC SUPERFLEX 550
69569	1,133	PLASTIC SUPERFLEX 505
69570	1,132	PLASTIC SUPERFLEX 425
69571	1,133	PLASTIC SUPERFLEX 432
69572	1,132	PLASTIC SUPERFLEX 405
69573	1,132	PLASTIC SUPER FLOW 400
69574	1,132	PLASTIC SUPER FLOW 390
69575	1,132	PLASTIC SUPERDENSE 700
69576	1,132	PLASTIC SUPERDENSE 710
69577	1,098	PLASTIC RESTOUR P
69578	1,098	PLASTIC RESTOUR V
69579	1,098	PLASTIC RESIOUR T
69580	1,098	PLASTIC RESIOUR AR
69581	905	PLASTIC ETS
69582	880	PLASTIC EHC
69583	905	PLASTIC ETS-FR-11
69584	880	PLASTIC EHG-S
69585	905	PLASTIC ETS-FR
69586	905	PLASTIC ETR-FR-C
69587	879	PLASTIC EGP-S
69588	943	PLASTIC HST11
69589	879	PLASTIC EFM
69590	904	PLASTIC ESG-S
69591	900	PLASTIC ESA-S
69592	932	PLASTIC H755

MSFC-HDBK-527 REV F 9999942 0006777 3

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
69593	937	PLASTIC HOSTAFLON TF
69594	937	PLASTIC HOSTAFLON TF1665
69595	938	PLASTIC HOSTAFLON TF4215
69596	938	PLASTIC HOSTAFLON TF4406
69597	938	PLASTIC HOSTAFLON TF2026
69598	938	PLASTIC HOSTAFLON TF2053
69599	938	PLASTIC HOSTAFLON TF2103
69600	166	ADHESIVE FILM FM300K
69601		DELETED SEE 62240
69602	79	ADHESIVE CPVC CEMENT AA1106HB
69603	84	ADHESIVE DAP FUNTAK
69604	62	ADHESIVE CASTALL A
69605	231	ADHESIVE RTV 730/RTV 1200 PRIME COAT
69606	231	ADHESIVE RTV 732/RTV 1200 PRIME COAT
69609	10	ADHESIVE 738/1204 PRIMER
69610	231	ADHESIVE RTV 739
69611	231	ADHESIVE RTV 738
69612	144	ADHESIVE EPOTEK 415G
69613	155	ADHESIVE EPOXYLITE 203
69614	155	ADHESIVE EPOXYLITE 221/C307
69615	69	ADHESIVE CHEMLOK 2
69616		DELETED SEE 69615
69617		DELETED SEE 67644
69618	59	ADHESIVE CA3
69619	59	ADHESIVE CA4
69620	59	ADHESIVE CA40
69621	60	ADHESIVE CA40H
69622	60	ADHESIVE CA5
69623	60	ADHESIVE CA7
69624	60	ADHESIVE CA8
69625	60	ADHESIVE CA9
69626	107	ADHESIVE EC3430
69627	116	ADHESIVE ECP3446
69628	183	ADHESIVE LIGHTWELD 481
69629	10	ADHESIVE 76 RES 6140 (45/55)
69630	938	PLASTIC HOSTAFLON TF4103
69631	938	PLASTIC HOSTAFLON TF4105
69632	938	PLASTIC HOSTAFLON TF4303
69633	938	PLASTIC HOSTAFLON TF2024
69634	938	PLASTIC HOSTAFLON TF2051
69635	938	PLASTIC HOSTAFLON TF2071
69636	942	PLASTIC HOSTALEN LD
69637	942	PLASTIC HOSTALEN PP
69638	940	PLASTIC HOSTALEN
69639	943	PLASTIC HOSTAPULP
69640	942	PLASTIC HOSTALIT
69641	942	PLASTIC HOSTALIT Z
69642	943	PLASTIC HOSTAPOT
69643	943	PLASTIC HOSTYREN
69644	803	PLASTIC 5204
69645	803	PLASTIC 5205
69646	803	PLASTIC 5207
69647	803	PLASTIC 5210
69648	803	PLASTIC 5218
69649	803	PLASTIC 5225
69650	804	PLASTIC 5240
69651	804	PLASTIC 5260
69652	806	PLASTIC 6206
69653	806	PLASTIC 6230
69654	803	PLASTIC 5003
69655	804	PLASTIC 5602
69656	804	PLASTIC 5603
69657	804	PLASTIC 5604
69658	805	PLASTIC 6004
69659	805	PLASTIC 6007
69660	805	PLASTIC 6009
69661	804	PLASTIC 5701
69662	804	PLASTIC 5703
69663	804	PLASTIC 5704 (2)
69664	805	PLASTIC 5705 (2)
69665	805	PLASTIC 5707
69666	805	PLASTIC 5713
69667	805	PLASTIC 6001C2
69668	805	PLASTIC 6003
69669	804	PLASTIC 5405
69670	804	PLASTIC 5406G
69671	804	PLASTIC 5408G
69672	804	PLASTIC 5411G
69673	797	PLASTIC 1013(1)
69674	797	PLASTIC 1014(1,2)
69675	797	PLASTIC 1015
69676	797	PLASTIC 1016(1,3)
69677	797	PLASTIC 1017
69678	797	PLASTIC 1103(1)
69679	797	PLASTIC 1105(1)
69680	801	PLASTIC 3010
69681	801	PLASTIC 3012
69682	801	PLASTIC 3050
69683	801	PLASTIC 3060
69684	801	PLASTIC 3070
69685	801	PLASTIC 3080
69686	802	PLASTIC 3304(4)
69687	802	PLASTIC 3312
69688	807	PLASTIC 8000GK
69689	807	PLASTIC 8001KL
69690	807	PLASTIC 8004MR
69691	808	PLASTIC 8004ZR
69692	808	PLASTIC 8020GU
69693	809	PLASTIC 8080GW
69694	809	PLASTIC 8310GO
69695	809	PLASTIC 8310KO
69696	809	PLASTIC 8402TO
69697	809	PLASTIC 8420HK
69698	809	PLASTIC 8502HK
69699	809	PLASTIC 8602HJ
69700	809	PLASTIC 8462HR
69701	809	PLASTIC 8470HU
69702	810	PLASTIC 8752HF
69703	810	PLASTIC 8755HK
69704	810	PLASTIC 8762HR

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006778 5

MATCD	PAGE	DESIGNATION
69705	810	PLASTIC 8770HU
69706	807	PLASTIC 7001DJ
69707	807	PLASTIC 7200AF
69708	807	PLASTIC 7300GF
69709	807	PLASTIC 7300KF
69710	798	PLASTIC 2000GJ
69711	798	PLASTIC 2004MR
69712	798	PLASTIC 2085CW
69713	798	PLASTIC 1510LC
69714	798	PLASTIC 1510HC
69715	801	PLASTIC 3002GJ
69716	801	PLASTIC 3011SO
69717	802	PLASTIC 3303SK
69718	802	PLASTIC 331050
69719	802	PLASTIC 3420CK
69720	802	PLASTIC 3510HC
69721	1,022	PLASTIC NYLON MP/FILLED
69722	1,021	PLASTIC NYLON 6/12
69723	1,022	PLASTIC NYLON NAST TYPE 6
69724	811	PLASTIC ACETAL HOMOPOLYMER
69725	810	PLASTIC ACETAL COPOLYMER
69726	811	PLASTIC ACETAL GLASS FILLED
69728	1,003	PLASTIC NORYL
69730	1,095	PLASTIC RCAS 3600
69731	1,095	PLASTIC RCAS 0600
69732	1,095	PLASTIC RCAS 1200
69733	1,095	PLASTIC RCAS 4200
69734	865	PLASTIC DUOGARD
69735	1,054	PLASTIC POLY-CLEAR
69736	1,164	PLASTIC TFE FLUOROCARBON
69740	1,043	PLASTIC PLASTIC STEEL PUTTY
69741	1,122	PLASTIC STEEL LIQUID
69742	1,122	PLASTIC STEEL 5-MIN. PUTTY
69743	1,187	PLASTIC TITANIUM PUTTY
69744	817	PLASTIC ALUMINUM PUTTY
69745	817	PLASTIC ALUMINUM LIQUID
69746	818	PLASTIC ALUMINUM VERY LIQUID
69747	832	PLASTIC BRONZE PUTTY
69748	1,117	PLASTIC STAINLESS STEEL PUTTY
69749	838	PLASTIC CARBIDE PUTTY
69750	1,230	PLASTIC WEAR RESISTANT PUTTY
69751	1,230	PLASTIC WEAR RESISTANT LIQUID
69752	841	PLASTIC CERAMIC WEAR COMPOUND
69753	1,051	PLASTIC PLUMB REPAIR PUTTY
69754	832	PLASTIC BRUSHABLE CERAMIC COMPOUND
69755	935	PLASTIC HIGH TEMP CERAMIC PUTTY
69756	936	PLASTIC HIGH TEMP MOLD MAKER
69757	1,134	PLASTIC TANKITE II
69758	1,234	PLASTIC WET SURFACE REPAIR PUTTY
69759	908	PLASTIC FLOOR GRIP
69760	908	PLASTIC FLOOR PATCH
69761	907	PLASTIC FLEXANE 80 LIQUID
69762	907	PLASTIC FLEXANE 94 LIQUID
69763	908	PLASTIC FLEXANE PUTTY
69764	908	PLASTIC FLEXANE HIGH PERFORMANCE PUTTY
69765	908	PLASTIC FLEXANE BRUSHABLE URETHANE
69766	803	PLASTIC 5% GLASS FIBER/95% TFE
69769	833	PLASTIC CADCO NYLON CNT
69770	803	PLASTIC 5% GLASS FIBER/5%MOS2/75% TFE
69771	797	PLASTIC 15% GLASS FIBER/5%MOS2/80% TFE
69772	797	PLASTIC 12.5% GLASS FIBER/12.5% MOS2/75% TFE
69773	802	PLASTIC 40% BRONZE/60% TFE
69774	805	PLASTIC 60% BRONZE/40% TFE
69775	807	PLASTIC 70% BRONZE/30% TFE
69776	802	PLASTIC 40% BRONZE/5% MOS2/55% TFE
69777	832	PLASTIC BRONZE/5% MOS2/40% TFE
69778	797	PLASTIC 10% CARBON-GRAPHITE/90% TFE
69779	800	PLASTIC 25% CARBON-GRAPHITE/75% TFE
69780	802	PLASTIC 35% CARBON-GRAPHITE/65% TFE
69781	833	PLASTIC CADCO NYLON CMD
69782	833	PLASTIC CADCO NYLON CBL
69783	856	PLASTIC DELRIN
69784	834	PLASTIC CADCO TYPE 6/6
69785	834	PLASTIC CADCO TYPE 6
69786	838	PLASTIC CAST NYLON POLYAMIDE TYPE 6
69787	833	PLASTIC CADCO NSM POLYAMIDE FILLED 6
69788	833	PLASTIC CADCO MD POLYAMIDE MDS2 FILL
69789	1,054	PLASTIC POLYACETAL HOMOPOLYMER
69790	1,023	PLASTIC OILON PV80 POLYACETAL FILLED HOMO
69791	858	PLASTIC DELRIN AF POLYACETAL FILLED HOMO
69792	834	PLASTIC CADCO UHMW
69793	833	PLASTIC CADCO CAST ACRYLIC
69795	1,390	SEALANT POLYSULFIDE PR1201 RLS
69796	1,413	TAPE ALUMINUM FOIL/GLASS CLOTH 2922-7
69797	141	ADHESIVE EPON 828/VERSAMID 828/VERSAMID 125
69798	125	ADHESIVE EPIBOND 1537
69799	1,256	POTTING COMPOUND SCOTCHCAST 251
69800	1,333	RUBBER SILICONE CV2942
69801	642	INSULATION FOAM SILICONE RTV DC3-6548
69802	399	COMPOUND ANTI-SEIZE ROYCO 44
69803	52	ADHESIVE BOSTIK 1009A/1008B
69804	633	INSULATION FOAM POLYURETHANE KIT FP60
69805		DELETED SEE 65960
69806	602	INSULATION CORK COMPOSITE P50
69807	1,238	PLASTIC ZELUX M131
69809	640	INSULATION FOAM SCOTT INDUSTRIAL
69810	1,532	WIRE ELEC SAMPLES V6.N22-9
69811	607	INSULATION FOAM CHEMLON POLYIMIDE
69812	383	COATING RTV DC Q36077 ABLATIVE/EPON 828/EPOCAST 951
69813	281	ARMALON IMPREGNATED WITH KRYTOX 143 AZ
69814	542	FILM METPOLY 100
69816	363	COATING MOLYKOTE 3400A CORROSION PROTECTIVE
69821	550	FILM ROSCOLUX 88/LIGHT GREEN COLOR FILTER
69822	356	COATING HUMISEAL 1B73
69823	363	COATING MEPCO FR14 CONFORMAL
69825	1,528	WIRE ELEC MD 913 FLUOROCARBON POLYIMIDE INSULATION
69828	271	ADHESIVE UNITAK 136
69830	1,398	SHOCK ABSORBER N5205-TXE
69831	393	COATING VARNISH HI-THERM BB252 BLACK BAKING

MSFC-HDBK-527 REV F 9999942 0006779 7

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
69833	38	ADHESIVE ARALDITE EPN1138/NADIC METHYL ANHYDRIDE N/N-DIMETHYL BENAYLAMIN
69836	639	INSULATION FOAM PYROCUSHION HF325-48
69837	639	INSULATION FOAM PYROCUSHION HF300-18
69843	447	FABRIC DISCOVERY 86U101-5 OI LAVENDER BLUE 80% WORSTED WOOL 20% RAYON
69844	503	FABRIC X-OGEN WOOL CORD #20 PETROL 80% WORSTED WOOL 20% KEVLAR CARBON
69845	579	HOSE TEFLON LINER (PROTION FROM HYDROCARBON SAMPLE LINE)
69846	640	INSULATION FOAM PYROTHANE LS
69847	225	ADHESIVE PRIMER CHEMLOK 205 RUBBER-TO-METAL
69848	680	LACING TAPE NYLON BRAID
69849	499	FABRIC TECKNIT 72-00008 FLEX CONDUCTIVE EPOXY S.F.
69850	362	COATING MEPCO FLEX
69851	274	ADHESIVE URALITE 3139 POLYURETHANE ORANGE
69853		DELETED SEE 65526
69854	659	INSULATION WIRE WHITE (PORTION FROM HYDROCARBON SAMPLE LINE)
69855	659	INSULATION WIRE GREEN (PORTION FROM HYDROCARBON SAMPLE LINE)
69856	550	FILM ROSCOLUX 51/SUPRISE PINK COLOR FILTER
69857	588	INK MARKEM 6887 BLACK AND 112XD THINNER
69858	1,467	TAPE WHITE WRAPPING (PORTION FROM HYDROCARBON SAMPLE LINE)
69859	499	FABRIC TECKNIT 72-00014
69860	1,426	TAPE LACING (PORTION FROM HYDROCARBON SAMPLE LINE)
69861	608	INSULATION FOAM CPR1061 COATED WITH ALBI-COTE FRL WITH COATED SEMICIRCLE
69863	482	FABRIC NYLON CHIFFON A5652/4
69865	1,477	THREAD NOMEX E77701/450 ROYAL BLUE SIZE 3/64
69866	573	HOSE FLEX DURAVENT U8 CLEAR
69867		DELETED SEE 66191
69872	1,488	TUBING HS HEATRAX 8509
69874	580	HOSE TEMPFLEX PLUS BLACK
69875	1,266	RED SHIELDING/SHEATH MATERIAL (PORTION FROM HYDROCARBON SAMPLE LINE)
69876	574	HOSE FLEX R19840X-032L
69877	671	LABELS PRES-A-PLY REMOVABLE
69878	407	CONNECTOR ELEC M24308/2-5
69879	407	CONNECTOR ELEC M24308/2-3
69880	670	LABEL ULTRACOLOR 17218 GREEN
69881	670	LABEL ULTRACOLOR 17219 YELLOW
69882	670	LABEL ULTRACOLOR 00093 KHAKI
69883	670	LABEL ULTRACOLOR 17215 PURPLE
69884	670	LABEL ULTRACOLOR 17220 ORANGE
69885	670	LABEL ULTRACOLOR 17214 BROWN
69886	670	LABEL ULTRACOLOR 17210 BLACK
69887	1,268	RETENTION OF HCI ON LAUNCH PLUME SAMPLER CHEMICAL FILTERS
69888	1,309	RUBBER OUTERWIRE CASING BLACK (PORTION FROM HYDROCARBON SAMPLE LINE)
69889	407	CONNECTOR ELEC M24308/1-2
69890	1,402	SOLIDOX TYPE "B" IGNITER
69891	1,458	TAPE SCOTCHCAL 8010 GREEN TRANSPARENT DYNAMARK
69892	1,458	TAPE SCOTCHCAL 8014 BLUE TRANSPARENT DYNAMARK
69893	1,317	RUBBER SANTOPRENE
69894	736	LUBE EMRALON 334
69895	298	CAST CAROPLASTIC PROPOSED FOR PPE
69896	1,410	STRAP CARBON GRAPHITE IM-6 EPOXY
69897	1,410	STRAP GLASS S2/EPOXY
69898	544	FILM MYLAR SHEET/POLLOK LOCKING ELEMENT GREEN
69899	1,513	WEBBING 22DPT-H
69900	537	FILM GORETEX 1/4" TFE PIPE SEALANT/NONADHESIVE
69901	537	FILM GORETEX 1/4" TFE PIPE SEALANT WITH ADHESIVE
69902	503	FABRIC X-OGEN CAVALRY TWILL LAVANDER 85% WOOL/15% KEVLAR
69903	73	ADHESIVE CHOBOND 584 CONDUCTIVE EPOXY
69904	408	CONNECTOR ELEC M24308/4-3
69905	434	FABRIC 800116-1 NEOPRENE-COATED NYLON
69906	908	PLASTIC FLUOROCARBON WAFER
69907	1,470	TEFLON PTFE RESIN (POWDERED RAW)
69908	1,492	TUBING LAMINATED/ROLLED PTFE RESIN/GLASS FABRIC BASE
69909	433	FABRIC 1213 TY1 CL1 NEOPRENE-COATED NYLON
69911	2	ABLEFILM 561 EPOXY ON GLASS 8/VERSAMID 115
69912	1,455	TAPE SCOTCH Y9360
69913	411	CONNECTOR ELECTRICAL SUBMINIATURE RECTANGULAR D/N RA2E12C0885N000 8241 OD
69914		DELETED SEE 66329
69916	1,051	PLASTIC PLEXIGLASS DR100
69917	186	ADHESIVE LOCTITE 69 HYDRAULIC SEALANT
69918		DELETED SEE 05247
69919	101	ADHESIVE EA9210H PR 10%
69920	101	ADHESIVE EA9210H PR 5%
69921	1,474	TETRA-ETCH FLUOROCARBON
69923	436	FABRIC ALUMINUM M11481
69924	1,377	RUBBER VITON O-RING 2-904
69925	556	FILTER NOMEX MEMBRANE
69926		DELETED SEE 20029
69927	1,528	WIRE ELEC MTV TYPE/PTFE KAPTON INSULATION
69928	1,523	WIRE ELEC 1871-2-169 PTFE KAPTON
69929		DELETED SEE 69927
69930		DELETED SEE 69921
69931		DELETED SEE 69927
69932		DELETED SEE 69927
69933	1,523	WIRE ELEC BTV 2-26-BF-9 PTFE KAPTON
69934		DELETED SEE 69927
69935		DELETED SEE 69927
69936	1,328	RUBBER SILICONE BMS 1-70 GR 40
69937	1,319	RUBBER SILASTIC 747
69938	619	INSULATION FOAM LS645C2
69940	16	ADHESIVE ABLEBOND 204-2
69942	290	CABLE COAX SILVER PLATED COPPER WITH PTFE KAPTON
69943	652	INSULATION KAOWOOL CONSORT ATF PLAIN
69944	710	LAMIN GRAPHITE HFT-G HONEYCOMB CORE
69945	374	COATING POLYURETHANE TOPCOAT #3
69946	374	COATING POLYURETHANE TOPCOAT #2
69947	608	INSULATION FOAM CPR1061 WITH ALBICOTE FRL
69949	1,536	WIRE ZINC METALLIZING

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006780 3

MATCD	PAGE	DESIGNATION
69950	807	PLASTIC 658/558
69951	671	LABELS BRADY XB652 HIGH TEMPERATURE
69952	643	INSULATION FOAM SONEX ACOUSTICAL FR
69953	670	LABELS BRADY 684 TEFLON
69954	505	FASTENER SCOTCHMATE HOOK SJ3419FR BLACK/ON BLACK NOMEX DUCK
69956	540	FILM KODACOLOR VR-G
69957	652	INSULATION KAOWOOL CONSORT ATF FOIL
69958	793	PEN FELT TIP PURPLE
69959	480	FABRIC NS456 ALUMINIZED POLYURETHANE NYLON
69960	585	INK CAT-L-INK 50-710/20
69961		DELETED SEE 63125
69962	584	INK CAT-L-INK 50-403R/20
69963	290	CABLE COAX RG179 PTFE CORE FEP JACKET SILVER COATED COPPER
69964	1,480	TILE FLEXCO A68 HW
69965	1,523	WIRE CABLE SHIELDED
69966	1,480	TILE FLEXCO SP40 HW
69967	583	INK 9900 ON LEXAN
69968	290	CABLE COAX RG6178 PTFE CORE FEP JACKET SILVER COATED COPPER
69969	1,480	TILE FLEXCO C10 HW
69970	1,401	SOAP DISH TRAVEL
69971	759	MASK SOLDER PC401 CLEAR
69972	760	MASK SOLDER PC401 GREEN
69973	760	MASK SOLDER PC501 CLEAR
69974	374	COATING POLYURETHANE TOPCOAT #1
69977	713	LAMIN PC BOARD #H3C WMCKT BRD DEVELOPMENT
69978	457	FABRIC GORTEX 1/8 TFE FLUOROCARBON JOINT SEALANT
69979		DELETED SEE 69974
69980	457	FABRIC GORTEX 1/8 TFE FLUOROCARBON PIPE SEALANT ADHES
69981		DELETED SEE 05339
69983	742	LUBE GREASE DC112 SILICONE
69984		DELETED SEE 05735
69985	668	LABEL IDENTIFICATION SCOTCHCAL 8006 RED/ TRANSPARENT
69986	590	INK MARKING K480 BLUE/BLACK FOIL
69987	345	COATING ENAMEL 15251A WHITE
69989	541	FILM MACTAC XD0002 ADHESIVE
69990	483	FABRIC NYLON POLYURETHANE COATED
69991		DELETED SEE 69927
69992	1,062	PLASTIC POLYPROPYLENE FILTRETE G108
69993	587	INK F600 MYLAR BLACK
69994	431	ETCHANT
69995	1,399	SILICA CAB-O-SIL M-5
77247	90	ADHESIVE DEVCON DK40
80000	1,538	Z STD AND COMMERCIAL PARTS
80001	1,538	Z MATL ID ON SUBCONTRACTR WKSH
80002	1,538	Z SUBSTITUTION INFO PRESENT
80003	420	CORD POLYESTER 80
80004	1,537	Z CONFIG ACCEPTION
80005	1,537	Z GFE
80006	1,538	Z NON-HAZARDOUS FLUID
80007	1,538	Z STANDARD COMM AND ME PART ID
80008	1,538	Z MATL ID ON PROD PART
80009	1,538	Z NOT TO BE USED ON SHUTTLE
80014	636	INSULATION FOAM PYRELL
80015	568	GRAPHITE BAR/100% GRAFOIL
80017		DELETED SEE 20894
80018	464	FABRIC KEVLAR EPOXY PANEL
80019	1,389	SEALANT OXY-TITE WITH TEFLON THREAD
80020	636	INSULATION FOAM PYRELL ACOUSTICAL
80022	1,262	POTTING COMPOUND TRIBO TDF5
80023	436	FABRIC ALUMINIZED NS458 POLYURETHANE COATED NYLON
80024	435	FABRIC ALUMINIZED NS452 POLYURETHANE COATED NYLON
80025	1,409	SPONGE RUBBER SILICONE RT 762 FR
80026	435	FABRIC ALUMINIZED DS662 POLYURETHANE POLYESTER COATED
80027	444	FABRIC COTTON SLEEP RESTRAINT
80028	1,401	SOAP NON-FOAMING
80029	424	DECALS AF-1-33/TAPE B-184
80030	462	FABRIC KEVLAR 102-123-2 COATED VITON
80031	1,402	SOLDER KESTER SN 96
80032	400	COMPOUND LEAK-TEC 160X
80033	400	COMPOUND LEAK-TEC FORMULA #277 NE
80034	649	INSULATION FOAM URETHANE PORON CELLULAR FR
80035		DELETED SEE 80017
80036	386	COATING SILICONE SEA200G ADHES
80037	412	CONNECTOR PC BOARD WTB90PR-7SY-X/WTB90SED-9SY-X
80038	1,507	VARNISH INPREGNATION IMIDALLOY TVB 2705
80041	1,252	POTTING COMPOUND KE45 SILICONE
80042	18	ADHESIVE ABLEBOND 731-1 EPOXY
80043	1,500	TUBING SUMITUBE POLYOLEFIN HST
80045	1,393	SEALANT SILICONE KE348
80046	1,337	RUBBER SILICONE KE941U
80047	1,325	RUBBER SILICONE 1671
80049	665	LABEL 71-6165 ALUMINIZED SIGHTING WITH PS ADHES
80050	469	FABRIC NOMEX 3 NO-MO-STAT WITH STAINLESS STEEL NAVY
80051	742	LUBE GREASE DC111 SILICONE
80052	581	IGNITION HAZARD PROOFING OF VLS ENVIRONMENTAL SAMPLERS
80053	435	FABRIC ALUMINIZED M11849-5 POLYURETHANE COATED
80054	1,535	WIRE P1W C-7 POLYIMIDE
80055	1,435	TAPE P21 GLASS
80056	757	MAGNETIC CORE T12-125
80057	183	ADHESIVE LOCTITE 221
80058	1,255	POTTING COMPOUND SCOTCHCAST 212
80059	322	COATING A276 WITH PGEA/515700/910704
80060	584	INK CAT-L-INK 50-508R/20
80061	584	INK CAT-L-INK 50-110/20
80062	101	ADHESIVE EA921NA EPOXY
80063	187	ADHESIVE LOCTITE AV
80064	624	INSULATION FOAM PDL 4034/OVERCOATED WITH SEA 200G SILICONE ELASTOMERIC ADHESIVE
80065	339	COATING DAPCO 2031 FLUOROELASTOMER
80066	955	PLASTIC LEXAN 2014 POLYCARBONATE
80067	664	KYNAR 740
80069	336	COATING CONATHANE EN2 POLYURETHANE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006781 5

MATCD	PAGE	DESIGNATION
80070	1,225	PLASTIC VICTREX PEEK 25% GLASS-FILLED
80071	420	CORD SHOCK RUBBER COVERED NYLON (BUNGEE)
80072	1,347	RUBBER SILICONE RTV 510
80073	957	PLASTIC LEXAN 9034-112/A4T COATING OVER DC Q9-6312
80075	284	BATTERY DURACELL SIZE AA MN1500
80078	284	BATTERY RAYOVAC ALKALINE SIZE AA
80081	473	FABRIC NOMEX FDC 307 F/WP
80082	1,520	WEBBING NYLON NET AAES-236/BG 168
80084	336	COATING CHOSHIELD 596 A/B EPOXY
80085	284	BATTERY SUPRALIFE GOLD TIPPED KAA4 SIZE AA
80086	284	BATTERY EVERREADY ENERGIZER E91 SIZE AA
80087	1,513	WAX ORIGINAL PLEDGE AEROSOL
80088	319	COATING 850-204/851-214 GREEN
80090	685	LAMIN 3 PLY ALUMINUM FOIL
80091	444	FABRIC COTTON TWILL GRT8134
80092	587	INK F30 BLACK
80093	534	FILM COPPER/MYLAR
80094	450	FABRIC ELASTIC 0.75 WIDE
80095	642	INSULATION FOAM SILICONE RTF762/SF9650
80096	408	CONNECTOR ELECTRIC 84450
80097	408	CONNECTOR ELECTRIC G & HV
80098	527	FASTENER VELCRO STILAN HOOK WITH BINDER ADHESIVE 0399
80099	522	FASTENER VELCRO NYLON LOOP 2000 BACKING 0172
80100	526	FASTENER VELCRO STILAN HOOK BACKING 8299 AND POLYESTER LOOP 2000
80101	526	FASTENER VELCRO STILAN HOOK BACKING 0399 AND POLYESTER LOOP 2000 BACKING 0399
80102	289	CABLE 77 OHM TWINAX
80103	556	FILTER TYPE G THICKNESS G-0110
80104	485	FABRIC NYLON/URETHANE 1414 COATED/ALUMINIZED AND URESEAL CEMENT
80106		DELETED SEE 69952
80109		DELETED SEE 05832
80110		DELETED SEE 00016
80111	498	FABRIC SUNBRELLA FIRESIST 8601 ARTIC BLUE
80112	291	CABLE COAXIAL RG-58C/U
80114	702	LAMIN EPOXY/GRAPHITE COATED WITH SMOOTH TEDLAR
80115	703	LAMIN EPOXY/GRAPHITE COATED WITH TEXTURED TEDLAR
80119	761	MICRO-SWITCH 12TL1-1..
80123	631	INSULATION FOAM POLYURETHANE ET
80125	634	INSULATION FOAM POLYURETHANE S17-120B
80126	1,324	RUBBER SILICONE 1258
80127	665	LABEL 721 POLYESTER FILM WITH B196 PS ADHES
80130	256	ADHESIVE TAKPAK
80131	482	FABRIC NYLON M11480 POLYURETHANE COATED
80133	405	CONNECTOR D-SUB ND101-9S-C/ND101-9P-C
80134	1,397	SEALANT WEATHERBAN 101 POLYSULFIDE
80135	793	PEN FELT TIP BEIGE
80136	505	FASTENER SCOTCHMATE LOOP SJ3418FR ON BLACK NOMEX DUCK 7.5 OZ
80137	636	INSULATION FOAM PUR EXP1 PANEL E
80138	635	INSULATION FOAM POUR EXP1
80139	349	COATING EPOXY POLYAMIDE RED 11105
80140	788	PAPER FILTER WHATMAN #1
80141	788	PAPER FILTER WHATMAN #42
80142	736	LUBE EMRALON 337
80143	465	FABRIC M11673 ALUMINIZED POLYURETHANE COATED NYLON
80144		DELETED SEE 06115
80145	331	COATING CHEMGLAZE A571 RED
80146	331	COATING CHEMGLAZE A671 LIGHT GREEN
80147	331	COATING CHEMGLAZE A871 ORANGE
80148	331	COATING CHEMGLAZE A971 YELLOW
80149	577	HOSE PLSS FLEX TEFLON LINED
80150	1,439	TAPE P69 PS
80151	341	COATING DC Z6040 SILANE
80152	1,442	TAPE PTFE EXPANDED/NON ADHESIVE
80153	597	INK TY609 MARKING BLACK
80154	328	COATING CAMIE 2000 ACRYLIC SPRAY
80155	451	FABRIC FIBERGLASS NOC
80156		DELETED SEE 05727
80157	750	LUBE GREASE UNITEMP 500
80158	640	INSULATION FOAM SCOTT CUSTOM GRADE 80 PPI
80159	1,505	TUNGSTEN CARBIDE
80160	1,505	TUNGSTEN CARBIDE AFBMA GRADE 25
80161	1,505	TUNGSTEN CARBIDE CARBOLOX GRADE 44
80162	1,505	TUNGSTEN CARBIDE KENNAMETAL 601
80163	1,505	TUNGSTEN CARBIDE K-96
80164	1,468	TEFLON ASBESTOS IMPREGNATED
80165	484	FABRIC NYLON URETHANE-CARBON IMPREGNATED COATED
80166	582	INK 57377 YELLOW/K10 PAPER
80167	788	PAPER GRAPHICS CONTROL ELECTROSTATIC COPY P/N 4036R WITH VERSATEC TYPE H/V80 TONER
80168	1,482	TOOTHPASTE NASADENT (NO TUBE)
80169	782	NYLON 2257 ALUM-INIZED NEOPRENE COATED WITH 2310 NEOPRENE BIAS TAPE AND N-1030 NEOPRENE ADHESIVE
80170	240	ADHESIVE SCOTCHWELD AF191 STRUCTURAL FILM
80171	540	FILM KIMFOIL
80172	534	FILM CR39
80173	587	INK HIGGINS BLACK MAGIC WATERPROOF INDIA 4465
80174	347	COATING EPICO 2000 (SG054, SG116) EPOXY PAINT
80175	493	FABRIC PYROMEX A-201
80176	791	PAPER STRATHMORE SHEETS 100% COTTON FIBER SERIES 500 WHITE POSTERBOARD
80177	582	INK 51022 GREEN/K10 PAPER
80178	1,394	SEALANT SILICONE KE44
80179	793	PEN FISHER SPACE REFILL P/N PR6 PURPLE MEDIUM POINT
80180	793	PEN FISHER SPACE REFILL P/N PR9 LIGHT BLUE MEDIUM POINT
80181	354	COATING HAMMER NET 300 PAINT CAR WHITE
80182	1,485	TUBING FEP SPIRAL SPF61
80183	304	CLAMP HIGH THERMAL KCA-44
80184	154	ADHESIVE EPOXY RESIN RE103
80185	548	FILM POLAROID 669 POLACOLOR ER INSTANT PACK
80189	1,437	TAPE P263 NOMEX/ACRYLIC (CREPE)
80190	470	FABRIC NOMEX 6 OZ WASHED IN BOLD 3 TWICE AND DRIED WITH BOUNCE TWICE
80191	293	CABLE F-12PWMS HIFLON
80192	534	FILM CRONAPAQUE CPF7 WHITE SEMI-OPAQUE

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006782 7

MATCD	PAGE	DESIGNATION
80193	1,271	RUBBER BAND NATURAL OR SYNTHETIC SIZE 64
80194	1,489	TUBING IDEMITSU POLYCARBONATE A2500
80195	1,242	POLYCARBONATE TAKIRON PANLITE PLATE
80196	295	CABLE MULTI JUNFLON 854-048A PTFE
80197	1,242	POLYCARBONATE PANLITE L1250
80198	534	FILM CRP POLYETHYLENE ANTISTATIC P/N B0214
80199	1,298	RUBBER LATEX DIAMOND CLEAR 11-INCH BALLOON
80200	1,371	RUBBER VITON 840627 (1320-75)
80201	1,414	TAPE BUNDLING GLASS FABRIC
80202	534	FILM CRONALAR HIGH ACUTANCE HA4 CRONAR CLEAR POLYESTER HIGH CONTRAST NEGATIVE WORKING FILM
80203	534	FILM CRONALAR HIGH ACUTANCE HA7 CRONAR CLEAR POLYESTER HIGH CONTRAST NEGATIVE WORKING FILM
80204	392	COATING URETHANE 03W127
80205	571	HARNESS PROTECTOR TEFLON GROMMET EDGING KG-023F
80206	371	COATING POLYTHANE CP500 SERIES/VINYL PHENOLIC VPP-702 PRIMER
80207	406	CONNECTOR ELASTOMERIC ZEBRA STRIPS FSC-C-.002 PITCH
80208	1,266	RESIN CALIBRE 800-4 POLYCARBONATE .10 INCH SHEET STANDARD BLACK 770001
80209	600	INSULATION BLACK FROM STRANDED ELECTRICAL WIRE
80210	535	FILM EKTACHROME SO251 HIGH SPEED VIDEO NEWS
80211	405	CONNECTOR D-SUB ND101-50S-C ND101-50P-C
80218	498	FABRIC STRAP CONTAINER COVER ND-3010 C/#1
80234	257	ADHESIVE THERMAL CONDUCTIVE A140 FR R1
80235	614	INSULATION FOAM DIVINYCELL HT-50
80236	481	FABRIC NYLON 2257 NEOPRENE COATED BONDED WITH SHORE CHEMICAL UBS-N1030 ADHESIVE AND NEOPRENE COATED NYLON TAP
80237	605	INSULATION FOAM CELLULAIRE H920A PVC
80239	370	COATING POLYFLON SPRAY WAX
80240	291	CABLE COAXIAL THERMAX RGU142 OVERLAID WITH EXPANDO HR HALAR SLEEVING
80241	658	INSULATION THERMAL RI409/SLS 213B NOMEX
80242	51	ADHESIVE BONDING LM52 T46
80243	643	INSULATION FOAM SONEX 1 FR POROUS ACOUSTIC MELAMINE HYPALON COATED
80244	1,379	RUBBER VITON O-RING V909-90
80245	441	FABRIC COTTON COVERALL (DRY-CLEANED 25 TIMES)
80246	441	FABRIC COTTON COVERALL (WASHED/DRIED 25 TIMES)
80247	473	FABRIC NOMEX COVERALL (WASH/DRIED 25 TIMES)
80248	437	FABRIC BASE-TREATED COTTON AMMONIA CURE WITH NASA TOPPING (DRY-CLEANED)
80249	437	FABRIC BASE-TREATED COTTON AMMONIA CURE WITH NASA TOPPING (WASHED/DRIED 25 TIMES)
80250	1,300	RUBBER MOSITES 10238
80251	654	INSULATION PIPE ARMAFLEX AP
80252	539	FILM KAPTON HF POLYIMIDE
80253	1,506	VARNISH DAISO DAP TYPE A
80254	527	FASTENER VELCRO STILAN LOOP 0399
80255	790	PAPER PHOTO 78 PLUS F COLOR PRINT MATERIAL
80256	789	PAPER INDEX LONG GRAIN PULP WOOD FIBER MATERIAL
80257	1,260	POTTING COMPOUND STYCAST 2850GT/C11
80259	498	FABRIC STILAN 541 WOVEN
80260	1,266	RESIN CALIBRE 700-4 POLYCARBONATE COLOR #030003
80261	1,428	TAPE MOLDED HOOK ULTENE PLASTIC EX1
80264	1,482	TOOTHPASTE NASADENT IN TUBE
80266	1,460	TAPE SHURTAPE PC28F B/L B1255
80267	1,236	PLASTIC YELLOW VINYL CAPS FORMULA 701
80268	555	FILM VINYL CLEAR UNPLASTICIZED WITH RUBBER RESIN ADHESIVE SYSTEM 14T-SS
80269	593	INK PRINTERS BLACK D6668 ON #60 SCOTT PAPER
80270	582	INK 61121 BROWN
80271	230	ADHESIVE RESIWELD FE7002 EPOXY
80272	197	ADHESIVE METHACRYLATE MX611
80274	293	CABLE ELECTRICAL SEA BL125
80275	293	CABLE ELECTRICAL 07145 AG COATED CU WITH TEFLON AND ALUMINIZED MYLAR
80276	523	FASTENER VELCRO PEEK HOOK AND LOOP
80277	293	CABLE FIBER OPTIC VSC-A1-10-17
80278	1,437	TAPE P422 TEFLON/SILICONE
80279	293	CABLE FIBER OPTIC OC-1050
80280	1,500	TUBING TEFLON 350 DISPOSAL
80281	371	COATING POLYURETHANE CLEAR GLOSS VARNISH ON INSTA-FOAM A67 V1
80282	666	LABEL BAR CODE ACRYLIC
80283	618	INSULATION FOAM ISOCYANURATE S17-120B
80284	1,435	TAPE P100 ALUMINUM FOIL/GLASS CLOTH WITH SILICONE ADHESIVE
80285	1,438	TAPE P5001 SILICONE RUBBER/GLASS CLOTH/SILICONE ASH
80286	1,438	TAPE P430 TEFLON WITH PS
80287	1,437	TAPE P262 NOMEX ARAMID FLATBACK ELEC INSULATION/ SILICONE ADHESIVE
80288	1,368	RUBBER URETHANE CYANAPRENE 3090
80289	168	ADHESIVE FM73M ON GRAPHITE EPOXY PLATES T50/934
80290	617	INSULATION FOAM INTERFLO HIGH MOLECULAR WEIGHT POLYETHYLENE
80291	1,503	TUBING THINWALL P100 SQUARE FORM SPIRAL WRAPPED
80292	561	FOAM INTERFLO HIGH MOLECULAR WEIGHT POLYETHYLENE HYDROPHOBIC FLAME RETARDANT
80293	533	FILM ANTI-STATIC WITH GRIDS
80294	552	FILM SCOTT CUSTOM GRADE
80295	1,415	TAPE CHOFOIL 101 COPPER FOIL
80296	1,499	TUBING SILASTIC P/N VWR62999-405
80297	366	COATING PAINT YELLOW 33798 URETHANE/PRIMER EPOXY AMIDE
80298	957	PLASTIC LEXAN 9034-112
80299	1,528	WIRE ELEC P/N ON365474-1
80300	413	CONNECTOR PIN MUPAC 108/NYLAFIL G20/40
80301	1,294	RUBBER KALREZ 1018
80303	671	LABELS THERMOFIT SLIP-ON HT TMS CM
80305	562	GASKET GYLON 1/16"
80315	1,438	TAPE P424 TEFLON
80318	508	FASTENER VELCOIN ON VINYL DISK/NYLON HOOK PS 0107
80319	914	PLASTIC FORMION FI105
80320	914	PLASTIC FORMION FI107
80321	914	PLASTIC FORMION FI120
80322	914	PLASTIC FORMION FI139

MSFC-HDBK-527 REV F 9999942 0006783 9

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
80323	914	PLASTIC FORMION FI147
80324	914	PLASTIC FORMION FI217
80325	914	PLASTIC FORMION FI241
80326	915	PLASTIC FORMION FI280
80327	1,056	PLASTIC POLYFLAM RCP762
80328	1,056	PLASTIC POLYFLAM RCP770C
80329	1,056	PLASTIC POLYFLAM RHD260ND (E)
80330	1,056	PLASTIC POLYFLAM RHD260ND RLP426
80331	1,056	PLASTIC POLYFLAM RMS424
80332	1,057	PLASTIC POLYFLAM RMS424E
80333	1,057	PLASTIC POLYFLAM RPP1021
80334	1,057	PLASTIC POLYFLAM RPP1058
80335	1,057	PLASTIC POLYFLAM RPP1062C
80336	1,057	PLASTIC POLYFLAM RPP1174
80337	1,057	PLASTIC POLYFLAM RPP932
80338	1,057	PLASTIC POLYFLAM RPP958
80339	1,057	PLASTIC POLYFLAM RPP958E
80340	1,057	PLASTIC POLYFLAM RPP982
80341	1,057	PLASTIC POLYFLAM RPP985
80342	1,057	PLASTIC POLYFLAM RS425C3
80343	1,057	PLASTIC POLYFORT FPP1006
80344	1,057	PLASTIC POLYFORT FPP1007
80345	1,057	PLASTIC POLYFORT FPP1182
80346	1,058	PLASTIC POLYFORT FPP1200
80347	1,058	PLASTIC POLYFORT FPP1223
80348	1,058	PLASTIC POLYFORT FPP1227
80349	1,058	PLASTIC POLYFORT FPP1237
80350	1,058	PLASTIC POLYFORT FPP1244
80351	1,058	PLASTIC POLYFORT FPP1245
80352	1,058	PLASTIC POLYFORT FPP1257
80353	1,058	PLASTIC POLYFORT FPP1272
80354	1,058	PLASTIC POLYFORT FPP1309
80355	1,058	PLASTIC POLYFORT FPP1310
80356	1,058	PLASTIC POLYFORT FPP1337
80357	1,058	PLASTIC POLYFORT FPP1345
80358	1,058	PLASTIC POLYFORT FPP1383
80359	1,058	PLASTIC POLYFORT FPP1488
80360	1,059	PLASTIC POLYFORT FPP1494
80361	1,059	PLASTIC POLYFORT FI?1512
80362	1,059	PLASTIC POLYFORT FI'1564
80363	1,059	PLASTIC POLYFORT FPP1578
80364	1,059	PLASTIC POLYFORT FPP1607
80365	1,059	PLASTIC POLYFORT FPP1608
80366	1,059	PLASTIC POLYFORT FPP1609
80367	1,059	PLASTIC POLYFORT FPP1611
80368	1,059	PLASTIC POLYFORT FPP1612
80369	1,059	PLASTIC POLYFORT FPP1650
80370	1,059	PLASTIC POLYFORT FPP1651
80371	1,059	PLASTIC POLYFORT FPP1652
80372	1,059	PLASTIC POLYFORT FPP1653
80373	1,059	PLASTIC POLYFORT FPP1654
80374	1,060	PLASTIC POLYFORT FPP1666
80375	1,060	PLASTIC POLYFORT PP1531
80376	1,060	PLASTIC POLYFORT PP1549
80377	1,060	PLASTIC POLYFORT PP828
80378	1,060	PLASTIC POLYFORT PP829
80379	1,060	PLASTIC POLYMAN 506
80380	1,060	PLASTIC POLYMAN 507
80381	1,060	PLASTIC POLYMAN 508
80382	1,060	PLASTIC POLYMAN 509
80383	1,060	PLASTIC POLYMAN 510
80384	1,060	PLASTIC POLYMAN 511
80385	1,060	PLASTIC POLYMAN 526
80386	1,060	PLASTIC POLYMAN 551
80387	1,060	PLASTIC POLYMAN 552
80388	1,061	PLASTIC POLYMAN 554
80389	1,061	PLASTIC POLYMAN 558
80390	1,066	PLASTIC POLYTROPE TPP1201
80391	1,066	PLASTIC POLYTROPE TPP293
80392	1,066	PLASTIC POLYTROPE TPP300
80393	1,066	PLASTIC POLYTROPE TPP309
80394	1,066	PLASTIC POLYTROPE TPP313
80395	1,066	PLASTIC POLYTROPE TPP317
80396	1,066	PLASTIC POLYTROPE TPP318
80397	1,066	PLASTIC POLYTROPE TPP319
80398	1,067	PLASTIC POLYTROPE TPP320
80399	1,067	PLASTIC POLYTROPE TPP334
80400	1,067	PLASTIC POLYTROPE TPP336
80401	1,067	PLASTIC POLYTROPE TPP337
80402	1,067	PLASTIC POLYTROPE TPP338
80403	1,067	PLASTIC POLYTROPE TPP341
80404	1,067	PLASTIC POLYTROPE TPP377
80405	1,067	PLASTIC POLYTROPE TPP393
80406	1,067	PLASTIC POLYTROPE TPP394
80407	1,067	PLASTIC POLYTROPE TPP402
80408	1,067	PLASTIC POLYTROPE TPP403
80409	1,067	PLASTIC POLYTROPE TPP408
80410	1,067	PLASTIC POLYTROPE TPP409
80411	1,067	PLASTIC POLYTROPE TPP414
80412	1,068	PLASTIC POLYTROPE TPP420
80413	1,068	PLASTIC POLYTROPE TPP421
80414	1,068	PLASTIC POLYTROPE TPP425
80415	1,068	PLASTIC POLYTROPE TPP427
80416	1,068	PLASTIC POLYTROPE TPP433
80417	1,068	PLASTIC POLYTROPE TPP442
80418	1,068	PLASTIC POLYTROPE TPP443
80419	1,068	PLASTIC POLYTROPE TPP444
80420	1,068	PLASTIC POLYTROPE TPP445
80421	1,068	PLASTIC POLYTROPE TPP446
80422	1,068	PLASTIC POLYTROPE TPP447
80423	1,068	PLASTIC POLYVIN 4507
80424	1,068	PLASTIC POLYVIN 5004
80425	1,068	PLASTIC POLYVIN 5023
80426	1,069	PLASTIC POLYVIN 5514
80427	1,069	PLASTIC POLYVIN 5802
80428	1,069	PLASTIC POLYVIN 5813
80429	1,069	PLASTIC POLYVIN 5819
80430	1,069	PLASTIC POLYVIN 5824
80431	1,069	PLASTIC POLYVIN 6110
80432	1,069	PLASTIC POLYVIN 6415

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006784 0

MATCD	PAGE	DESIGNATION
80433	1,069	PLASTIC POLYVIN 6424
80434	1,069	PLASTIC POLYVIN 6588
80435	1,069	PLASTIC POLYVIN 6614
80436	1,069	PLASTIC POLYVIN 6618
80437	1,069	PLASTIC POLYVIN 6713
80438	1,069	PLASTIC POLYVIN 6820
80439	1,069	PLASTIC POLYVIN 6825
80440	1,070	PLASTIC POLYVIN 6837
80441	1,070	PLASTIC POLYVIN 7112
80442	1,070	PLASTIC POLYVIN 7125
80443	1,070	PLASTIC POLYVIN 7180
80444	1,070	PLASTIC POLYVIN 7280
80445	1,070	PLASTIC POLYVIN 7427
80446	1,070	PLASTIC POLYVIN 7522
80447	1,070	PLASTIC POLYVIN 7532
80448	1,070	PLASTIC POLYVIN 7601
80449	1,070	PLASTIC POLYVIN 7709
80450	1,070	PLASTIC POLYVIN 7856
80451	1,070	PLASTIC POLYVIN 7911
80452	1,070	PLASTIC POLYVIN 8058
80453	1,070	PLASTIC POLYVIN 8101
80454	1,071	PLASTIC POLYVIN 8110
80455	1,071	PLASTIC POLYVIN 8111
80456	1,071	PLASTIC POLYVIN 8124
80457	1,071	PLASTIC POLYVIN 8125
80458	1,071	PLASTIC POLYVIN 8222
80459	1,071	PLASTIC POLYVIN 8380
80460	1,071	PLASTIC POLYVIN 8384
80461	1,071	PLASTIC POLYVIN 8428
80462	1,071	PLASTIC POLYVIN 8540
80463	1,071	PLASTIC POLYVIN 8546
80464	1,071	PLASTIC POLYVIN 8612
80465	1,071	PLASTIC POLYVIN 8803
80466	1,071	PLASTIC POLYVIN 8813
80467	1,071	PLASTIC POLYVIN 8819
80468	1,072	PLASTIC POLYVIN 8820
80469	1,072	PLASTIC POLYVIN 8822
80470	1,072	PLASTIC POLYVIN 8835
80471	1,072	PLASTIC POLYVIN 9009
80472	1,072	PLASTIC POLYVIN 9044
80473	1,072	PLASTIC POLYVIN 9108
80474	1,072	PLASTIC POLYVIN 9226
80475	1,072	PLASTIC POLYVIN 9400
80476	1,072	PLASTIC POLYVIN 9533
80477	1,133	PLASTIC SUPEROHM 3728
80478	20	ADHESIVE ABLEBOND 84-1LMI S1
80479	20	ADHESIVE ABLEBOND 85-1
80480	21	ADHESIVE ABLEBOND 968-2
80481	21	ADHESIVE ABLEBOND 969-1
80482	21	ADHESIVE ABLEBOND SG2001
80483	21	ADHESIVE ABLEBOND SG2002
80484	22	ADHESIVE ABLEFILM 563
80485	22	ADHESIVE ABLEFILM 563K
80486	23	ADHESIVE ABLEFILM 564K
80487	23	ADHESIVE ABLEFILM ECF563

MATCD	PAGE	DESIGNATION
80488	811	PLASTIC ADELL AB14
80489	811	PLASTIC ADELL AB16
80490	811	PLASTIC ADELL AB18
80491	811	PLASTIC ADELL AF10-660
80492	811	PLASTIC ADELL AF10-667
80493	812	PLASTIC ADELL AF10-667A
80494	812	PLASTIC ADELL AF10-667B
80495	812	PLASTIC ADELL AG16-662
80496	812	PLASTIC ADELL AH18
80497	812	PLASTIC ADELL AL18
80498	812	PLASTIC ADELL AM10
80499	812	PLASTIC ADELL AN38
80500	812	PLASTIC ADELL AO16
80501	812	PLASTIC ADELL AR13
80502	812	PLASTIC ADELL AR14
80503	812	PLASTIC ADELL AR16
80504	812	PLASTIC ADELL AR18
80505	812	PLASTIC ADELL AT13
80506	812	PLASTIC ADELL AT14
80507	813	PLASTIC ADELL AT16
80508	813	PLASTIC ADELL BH18
80509	813	PLASTIC ADELL BL18
80510	813	PLASTIC ADELL BR13
80511	813	PLASTIC ADELL BR14
80512	813	PLASTIC ADELL BR16
80513	813	PLASTIC ADELL BR18
80514	813	PLASTIC ADELL BR310
80515	813	PLASTIC ADELL BY10
80516	813	PLASTIC ADELL EF10
80517	813	PLASTIC ADELL EP14
80518	813	PLASTIC ADELL EP16
80519	813	PLASTIC ADELL ER14
80520	813	PLASTIC ADELL ER16
80521	814	PLASTIC ADELL HR36
80522	814	PLASTIC ADELL KR14
80523	814	PLASTIC ADELL KR16
80524	814	PLASTIC ADELL KR18
80525	209	ADHESIVE PEN SEAL 50
80526	828	PLASTIC ASTRAGLAS K
80527	828	PLASTIC ASTRAGLAS N
80528	828	PLASTIC ASTRAGLAS NG
80529	904	PLASTIC ESTRALON PET
80530	926	PLASTIC GLASBORD S
80531	978	PLASTIC LUCITE CAST ACRYLIC
80532	1,017	PLASTIC NYLATRON NSB NYLON
80533	1,017	PLASTIC NYLATRON NSN NYLON
80534	1,054	PLASTIC POLY-GLAZ SHEET
80535	1,061	PLASTIC POLYPENCO 101 (NYLON 6/6)
80536	1,061	PLASTIC POLYPENCO 11
80537	1,061	PLASTIC POLYPENCO 12
80538	1,227	PLASTIC VIVAK SHEET
80539	996	PLASTIC NEOFLON PFA AP210
80540	996	PLASTIC NEOFLON PFA AP230
80541	856	PLASTIC DAIKIN TEFLON FEP NP30
80542	1,138	PLASTIC TEFZEL 200

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006785 2 ■

MATCD	PAGE	DESIGNATION
80543	1,138	PLASTIC TEFZEL 210
80544	1,138	PLASTIC TEFZEL 280
80545	1,227	PLASTIC VIXTRIX 450 CA30
80546	1,227	PLASTIC VIXTRIX 450G
80547	1,227	PLASTIC VIXTRIX 450GL30
80548	1,227	PLASTIC VIXTRIX D150CA30
80549	1,227	PLASTIC VIXTRIX D150G
80550	1,227	PLASTIC VIXTRIX D150GL30
80551	814	PLASTIC AKEMI AP1050
80552	814	PLASTIC AKEMI AP1075
80553	814	PLASTIC AKEMI AP1200
80554	814	PLASTIC AKEMI AP1600
80555	814	PLASTIC AKEMI AP2307
80557	814	PLASTIC AKEMI AP2309
80558	814	PLASTIC AKEMI AP2311
80559	814	PLASTIC AKEMI AP2316 55/45
80560	815	PLASTIC AKEMI FILLER 4
80561	815	PLASTIC AKEMI FILLER 7
80562	815	PLASTIC AKULON K222D
80563	815	PLASTIC AKULON K222F
80564	815	PLASTIC AKULON K223B2P1
80565	815	PLASTIC AKULON K223HMS6
80566	815	PLASTIC AKULON K224GO
80567	815	PLASTIC AKULON K224G3
80568	815	PLASTIC AKULON K224G5
80569	815	PLASTIC AKULON K224G6
80570	815	PLASTIC AKULON K224G7
80571	815	PLASTIC AKULON K224HM6
80572	815	PLASTIC AKULON M223D
80573	815	PLASTIC AKULON M231D1
80574	816	PLASTIC AKULON M238D1
80575	816	PLASTIC AKULON M921D
80576	816	PLASTIC AKULON S223D
80577	816	PLASTIC AKULON S223E
80578	816	PLASTIC AKULON S223F
80579	816	PLASTIC AKULON S223GO
80580	816	PLASTIC AKULON S223G3
80581	816	PLASTIC AKULON S223G5
80582	816	PLASTIC AKULON S223G6
80583	816	PLASTIC AKULON S223G7
80584	816	PLASTIC AKULON S223H2G6
80585	816	PLASTIC AKULON S223HM6
80586	816	PLASTIC AKULON S223HM8
80587	816	PLASTIC AKULON S223HMV7
80588	817	PLASTIC AKULON S240C
80589	825	PLASTIC ARNITEL 40D G1 G6
80590	825	PLASTIC ARNITEL 46D G1 G6
80591	825	PLASTIC ARNITEL 55D G1 G6
80592	1,241	PLASTICS ARNITEL 63D G1-G6
80593	826	PLASTIC ARNITEL 74D G1 G6
80594	826	PLASTIC ARNITEL EL550
80595	826	PLASTIC ARNITEL EL630
80596	826	PLASTIC ARNITEL EL740
80597	826	PLASTIC ARNITEL EM400
80598	826	PLASTIC ARNITEL EM460

MATCD	PAGE	DESIGNATION
80599	1,102	PLASTIC ROSITE 3250A
80600	1,102	PLASTIC ROSITE 3250C
80601	1,102	PLASTIC ROSITE 3550A
80602	1,102	PLASTIC ROSITE 3550C
80603	1,102	PLASTIC ROSITE 3550FM
80604	932	PLASTIC HALON TFE G18
80605	932	PLASTIC HALON TFE G700
80606	932	PLASTIC HALON TFE G80
80608	932	PLASTIC HALON TFE G83
80609	1,061	PLASTIC POLYMIST F-5
80610	1,061	PLASTIC POLYMIST F-510
80611	1,061	PLASTIC POLYMIST F-5A
80612	838	PLASTIC CAPRON 8267G
80613	1,025	PLASTIC PAXON AA55-600
80614	1,026	PLASTIC PAXON FD60-018
80615	57	ADHESIVE BR92A
80616	57	ADHESIVE BR95
80617		DELETED SEE 00708
80618	168	ADHESIVE FM137/BR127
80619	168	ADHESIVE FM238/BR238
80620	168	ADHESIVE FM330
80621	7	ADHESIVE 330U
80622	168	ADHESIVE FM350/BR154
80623	168	ADHESIVE FM3505/BR154
80624	168	ADHESIVE FM53/BR53
80625	168	ADHESIVE FM53U/BR53
80626	168	ADHESIVE FM61/BR227
80627	168	ADHESIVE FM61/BR227A
80628	168	ADHESIVE FM73/BR127
80629	168	ADHESIVE FM73/BR73
80630	169	ADHESIVE FM73M/BR127
80632	170	ADHESIVE FXM410
80633	937	PLASTIC HOSTAFLON TF1100
80634	937	PLASTIC HOSTAFLON TF1400
80635	937	PLASTIC HOSTAFLON TF1620
80636	937	PLASTIC HOSTAFLON TF1620F
80637	937	PLASTIC HOSTAFLON TF1640
80638	938	PLASTIC HOSTAFLON TF1740
80639	938	PLASTIC HOSTAFLON TF1760
80640	938	PLASTIC HOSTAFLON TF5032
80641	939	PLASTIC HOSTAFLON TF5033
80642	939	PLASTIC HOSTAFORM C13021
80643	939	PLASTIC HOSTAFORM C13031
80644	939	PLASTIC HOSTAFORM C2521
80645	939	PLASTIC HOSTAFORM C2541
80646	939	PLASTIC HOSTAFORM C27021
80647	939	PLASTIC HOSTAFORM C32021
80648	939	PLASTIC HOSTAFORM C32021AST
80649	939	PLASTIC HOSTAFORM C52021
80650	939	PLASTIC HOSTAFORM C9021
80651	939	PLASTIC HOSTAFORM C9021GV
80652	939	PLASTIC HOSTAFORM C9021K
80653	939	PLASTIC HOSTAFORM C9021M
80654	939	PLASTIC HOSTAFORM C9021TF
80655	940	PLASTIC HOSTAFORM S27063

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006786 4

MATCD	PAGE	DESIGNATION
80656	940	PLASTIC HOSTAFORM S27064
80657	940	PLASTIC HOSTAFORM S27073
80658	855	PLASTIC CYGLAS 620X
80659	940	PLASTIC HOSTAFORM S27076
80660	940	PLASTIC HOSTAFORM S9063
80661	940	PLASTIC HOSTAFORM S9064
80662	940	PLASTIC HOSTAFORM T1020
80663	940	PLASTIC HOSTALEN GA7260
80664	940	PLASTIC HOSTALEN GB6450
80665	940	PLASTIC HOSTALEN GC7260
80666	940	PLASTIC HOSTALEN GD4760
80667	940	PLASTIC HOSTALEN GD6250
80668	940	PLASTIC HOSTALEN GD7255
80669	941	PLASTIC HOSTALEN GF4750
80670	941	PLASTIC HOSTALEN GF4760
80671	941	PLASTIC HOSTALEN GF7740F
80672	941	PLASTIC HOSTALEN GF7740F2
80673	941	PLASTIC HOSTALEN GF7750M
80674	941	PLASTIC HOSTALEN GF9360K
80675	941	PLASTIC HOSTALEN GH4765
80676	941	PLASTIC HOSTALEN GM5010T2
80677	941	PLASTIC HOSTALEN GM5040
80678	941	PLASTIC HOSTALEN GM5040T12
80679	941	PLASTIC HOSTALEN GM5040T50
80680	941	PLASTIC HOSTALEN GM5050
80681	941	PLASTIC HOSTALEN GM6255
80682	942	PLASTIC HOSTALEN GM7255
80683	942	PLASTIC HOSTALEN GM7746
80684	942	PLASTIC HOSTALEN GM8255
80685	942	PLASTIC HOSTALEN GM9050F
80686	942	PLASTIC HOSTALEN GM9240HT
80687	942	PLASTIC HOSTALEN GM9255F
80688	942	PLASTIC HOSTALEN GM9350C
80689	941	PLASTIC HOSTALEN GM7040G
80690	942	PLASTIC HOSTALEN GM7745
80691	942	PLASTIC HOSTALEN GR7255P
80692	942	PLASTIC HOSTALEN GUR
80693	818	PLASTIC AMOCO CRYSTAL POLYSTYRENE G1
80694	818	PLASTIC AMOCO CRYSTAL POLYSTYRENE G18
80695	818	PLASTIC AMOCO CRYSTAL POLYSTYRENE G2
80696	818	PLASTIC AMOCO CRYSTAL POLYSTYRENE G3
80697	818	PLASTIC AMOCO CRYSTAL POLYSTYRENE R1
80698	818	PLASTIC AMOCO CRYSTAL POLYSTYRENE R2
80699	818	PLASTIC AMOCO CRYSTAL POLYSTYRENE R3
80700	818	PLASTIC AMOCO CRYSTAL POLYSTYRENE R5
80701	818	PLASTIC AMOCO CRYSTAL POLYSTYRENE R7
80702	818	PLASTIC AMOCO IMPACT POLYSTYRENE H2R
80703	818	PLASTIC AMOCO IMPACT POLYSTYRENE H3E
80704	818	PLASTIC AMOCO IMPACT POLYSTYRENE H4E
80705	819	PLASTIC AMOCO IMPACT POLYSTYRENE H4R
80706	819	PLASTIC AMOCO IMPACT POLYSTYRENE HXM
80707	819	PLASTIC AMOCO IMPACT POLYSTYRENE M9
80708	819	PLASTIC AMOCO IMPACT POLYSTYRENE M9R
80709	819	PLASTIC AMOCO POLYPROPYLENE 4017
80710	819	PLASTIC AMOCO POLYPROPYLENE 4018
80711	819	PLASTIC AMOCO POLYPROPYLENE 4036
80712	819	PLASTIC AMOCO POLYPROPYLENE 4039
80713	819	PLASTIC AMOCO POLYPROPYLENE 4046
80714	819	PLASTIC AMOCO POLYPROPYLENE 4222
80715	819	PLASTIC AMOCO POLYPROPYLENE 4228
80716	819	PLASTIC AMOCO POLYPROPYLENE 5219
80717	819	PLASTIC AMOCO POLYPROPYLENE 7232
80718	819	PLASTIC AMOCO POLYPROPYLENE 7234
80723	820	PLASTIC AMOCO POLYPROPYLENE CR22 NA
80724	820	PLASTIC AMOCO POLYPROPYLENE CR35 NA
80725	820	PLASTIC AMOCO POLYPROPYLENE CR35 A
80726	808	PLASTIC 8007
80727	808	PLASTIC 8016
80728	808	PLASTIC 8020
80729	808	PLASTIC 8022
80730	808	PLASTIC 8031
80731	808	PLASTIC 8038
80732	808	PLASTIC 8041
80733	808	PLASTIC 8049
80734	808	PLASTIC 8050
80735	808	PLASTIC 8057
80736	808	PLASTIC 8061
80737	808	PLASTIC 8068
80738	809	PLASTIC 8072
80739	809	PLASTIC 8079
80740	809	PLASTIC 8085
80741	809	PLASTIC 8086
80742	809	PLASTIC 8659
80743	40	ADHESIVE AREMCOBOND 529
80744	1,239	PLASTIC ZONAREZ 7115
80745	1,239	PLASTIC ZONAREZ 7115 LITE
80746	1,239	PLASTIC ZONAREZ 7125
80747	1,239	PLASTIC ZONAREZ 7125 LITE
80748	1,239	PLASTIC ZONAREZ ALPHA 25
80749	1,239	PLASTIC ZONAREZA B-115
80750	1,239	PLASTIC ZONAREZ B-125
80751	1,239	PLASTIC ZONAREZ M115
80752	1,239	PLASTIC ZONATAC 105
80753	1,239	PLASTIC ZONATAC 105 LITE
80754	1,239	PLASTIC ZONATAC 115 LITE
80755	1,239	PLASTIC ZONATAC 501
80756	1,239	PLASTIC ZONATAC 501 LITE
80757	1,239	PLASTIC ZONESTER 100
80758	1,240	PLASTIC ZONESTER 55
80759	1,240	PLASTIC ZONESTER 65
80760	1,240	PLASTIC ZONESTER 75
80761	1,240	PLASTIC ZONESTER 85
80762	15	ADHESIVE AA1618
80763	47	ADHESIVE AROPOL 7240
80764	175	ADHESIVE HETRON 700
80765	175	ADHESIVE HETRON 800
80766	213	ADHESIVE PLASTOMERIC SEALANT
80767	828	PLASTIC ATLAS POLYETHYLENE (LINEAR)
80768	828	PLASTIC ATLAS POLYPROPYLENE HOMOPOLYMER
80769	828	PLASTIC ATLAS POLYPROPYLENE V0 HOMOPOLYMER

MSFC-HDBK-527 REV F 9999942 0006787 6

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
80770	828	PLASTIC ATLAS POLYPROPYLENE V2 HOMOPOLYMER
80771	829	PLASTIC ATLAS PVC T2
80772	829	PLASTIC ATLASTAFLEX PVC SHEET MEMBRANE
80773	1,056	PLASTIC POLYETHYLENE (LINEAR)
80774	1,062	PLASTIC POLYPROPYLENE HOMOPOLYMER
80775	1,063	PLASTIC POLYPROPYLENE HOMOPOLYMER V-O
80776	1,062	PLASTIC POLYPROPYLENE HOMOPOLYMER V-2
80777	1,227	PLASTIC VPC TYPE 2
80778	913	PLASTIC FORAFLON 1000HD
80779	932	PLASTIC GSMRO2
80780	1,023	PLASTIC ORGAMIDE RMNO P40 CD
80781	1,023	PLASTIC ORGAMIDE RMNOCD
80782	1,023	PLASTIC ORGAMIDE RZM 30
80783	1,023	PLASTIC ORGAMIDE RZM15
80784	1,023	PLASTIC ORGATER TMNO
80785	1,023	PLASTIC ORGATER TZM 20
80786	1,023	PLASTIC ORGATER TZM 30 W8
80787	1,033	PLASTIC PEBAX 2533
80788	1,033	PLASTIC PEBAX 3533
80789	1,033	PLASTIC PEBAX 4011
80790	1,033	PLASTIC PEBAX 4033
80791	1,033	PLASTIC PEBAX 5512
80792	1,033	PLASTIC PEBAX 5533
80793	1,033	PLASTIC PEBAX 5562
80794	1,033	PLASTIC PEBAX 6312
80795	1,033	PLASTIC PEBAX 6333
80796	1,033	PLASTIC PEBAX SERIES 62
80797	1,099	PLASTIC RILSAN AECNO TL
80798	1,099	PLASTIC RILSAN AESNO P10 TL
80799	1,099	PLASTIC RILSAN AESNO P20 TL
80800	1,099	PLASTIC RILSAN AESNO P40 TL
80801	1,099	PLASTIC RILSAN AESNO TL
80802	1,099	PLASTIC RILSAN AMNO
80803	1,099	PLASTIC RILSAN AMNY
80804	1,099	PLASTIC RILSAN AUM 30
80805	1,099	PLASTIC RILSAN AZM 30
80806	1,099	PLASTIC RILSAN BECNO W3TL
80807	1,099	PLASTIC RILSAN BESNO
80808	1,099	PLASTIC RILSAN BESNO F15TL
80809	1,100	PLASTIC RILSAN P40TL
80810	1,099	PLASTIC RILSAN BMN G8
80811	1,099	PLASTIC RILSAN BMNO
80812	1,100	PLASTIC RILSAN BMNY
80813	1,100	PLASTIC RILSAN BZM23 BLK TL
80814	1,100	PLASTIC RILSAN BZM23G9
80815	1,100	PLASTIC RILSAN BZM43 BLK
80816	1,100	PLASTIC RILSAN BZM43G9
80817	1,100	PLASTIC RILSAN BZMO30
80818	1,100	PLASTIC RILSAN NYLON 12 MOLDING GRADE AZM23G9
80819	1,100	PLASTIC RILSAN NYLON 12 MOLDING GRADE AZN43G9
80820	1,018	PLASTIC NYLON 12 MOLDING GRADE AZMO30
80821	1,100	PLASTIC RILSAN SR100
80822	1,278	RUBBER COHRLASTIC 9255
80823	1,278	RUBBER COHRLASTIC 9275
80824	1,278	RUBBER COHRLASTIC 9750
80825	1,278	RUBBER COHRLASTIC 9770
80826	1,278	RUBBER COHRLASTIC 9855
80827	1,278	RUBBER COHRLASTIC R10450
80828	817	PLASTIC ALGOFLON 27
80829	817	PLASTIC ALGOFLON D60V
80830	817	PLASTIC ALGOFLON DF1
80831	817	PLASTIC ALGOFLON E2
80832	817	PLASTIC ALGOFLON F2
80833	932	PLASTIC HALAR FEP
80834	932	PLASTIC HALAR PTFE
80835	932	PLASTIC HALAR PVF2
80837	50	ADHESIVE BACON K31
80838	50	ADHESIVE BACON K50
80839	50	ADHESIVE BACON K5235
80840	978	PLASTIC LUCOBIT 1210
80841	978	PLASTIC LURAN 358N
80842	978	PLASTIC LURAN 368R
80843	978	PLASTIC LURAN 378P
80844	978	PLASTIC LURAN 378P7
80845	978	PLASTIC LURAN 388S
80846	978	PLASTIC LURAN S728K
80847	978	PLASTIC LURAN S757R/RE
80848	978	PLASTIC LURAN S776S/SE
80849	978	PLASTIC LURAN SKR2843
80850	978	PLASTIC LURAN SKR2853/1
80851	979	PLASTIC LUVICAN
80852	1,008	PLASTIC NOVOLEN 1120HX
80853	1,008	PLASTIC NOVOLEN 1120LX
80854	1,008	PLASTIC NOVOLEN 1120NX
80855	1,008	PLASTIC NOVOLEN 1300E
80856	1,008	PLASTIC NOVOLEN 1300Z
80857	1,008	PLASTIC NOVOLEN 1320H
80858	1,008	PLASTIC NOVOLEN 1320L
80859	1,008	PLASTIC NOVOLEN 3300HX
80860	1,023	PLASTIC PALATAL P6 30/35% GLASS
80861	1,024	PLASTIC PALATAL P6 40/45% GLASS
80862	1,024	PLASTIC PALATAL P6 50/55% GLASS (IB)
80863	1,024	PLASTIC PALATAL P6 55/60% GLASS
80864	1,024	PLASTIC PALATAL P6 60/70% GLASS
80865	1,024	PLASTIC PALATAL P6 70/75% GLASS
80866	1,024	PLASTIC PALATAL P6 UNREINFORCED
80867	1,064	PLASTIC POLYSTYROL 143E
80868	1,064	PLASTIC POLYSTYROL 144C
80869	1,064	PLASTIC POLYSTYROL 158KG6
80871	1,064	PLASTIC POLYSTYROL 165H
80872	1,064	PLASTIC POLYSTYROL 168N
80873	1,064	PLASTIC POLYSTYROL 427D
80874	1,065	PLASTIC POLYSTYROL 432B
80875	1,065	PLASTIC POLYSTYROL 454C
80876	1,065	PLASTIC POLYSTYROL 454H
80877	1,065	PLASTIC POLYSTYROL 456M
80878	1,065	PLASTIC POLYSTYROL 466I
80879	1,065	PLASTIC POLYSTYROL 472C
80880	1,065	PLASTIC POLYSTYROL 473D
80881	1,065	PLASTIC POLYSTYROL 475K

MSFC-HDBK-527 REV F 9999942 0006788 8

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
80882	1,065	PLASTIC POLYSTYROL 476L
80883	1,065	PLASTIC POLYSTYROL KR2711
80884	1,065	PLASTIC POLYSTYROL KR2751
80885	1,065	PLASTIC POLYSTYROL KR2791
80886	1,065	PLASTIC POLYSTYROL SB2710
80887	1,130	PLASTIC STYRODUR 3000
80888	1,130	PLASTIC STYRODUR 4000
80889	1,130	PLASTIC STYRODUR 5000
80890	1,159	PLASTIC TERLURAN 828P
80891	1,159	PLASTIC TERLURAN 848S
80892	1,159	PLASTIC TERLURAN 857N
80893	1,159	PLASTIC TERLURAN 867M
80894	1,159	PLASTIC TERLURAN 877T/TE
80895	1,159	PLASTIC TERLURAN 886T
80896	1,159	PLASTIC TERLURAN 957SE
80897	1,160	PLASTIC TERLURAN 967K
80898	1,160	PLASTIC TERLURAN 978T
80899	1,160	PLASTIC TERLURAN 997VE
80900	1,160	PLASTIC TERLURAN KR2543
80901	1,160	PLASTIC TERLURAN KR2802/1
80902	1,160	PLASTIC TERLURAN KR2882
80903	1,194	PLASTIC ULTRADUR B4300G2
80904	1,194	PLASTIC ULTRADUR B4300G4
80905	1,194	PLASTIC ULTRADUR B4300G6
80906	1,194	PLASTIC ULTRADUR B4305G6
80907	1,194	PLASTIC ULTRADUR B4500
80908	1,194	PLASTIC ULTRADUR B4520
80909	1,194	PLASTIC ULTRADUR KR4015
80910	1,194	PLASTIC ULTRADUR KR4025
80911	1,194	PLASTIC ULTRADUR KR4035
80912	1,194	PLASTIC ULTRADUR KR4300K4
80913	1,194	PLASTIC ULTRAFORM H2200G5
80914	1,194	PLASTIC ULTRAFORM H2320
80915	1,194	PLASTIC ULTRAFORM N2320
80916	1,195	PLASTIC ULTRAFORM S2320
80917	1,195	PLASTIC ULTRAFORM W2320
80918	1,195	PLASTIC ULTRAMID A25
80919	1,195	PLASTIC ULTRAMID A3
80920	1,195	PLASTIC ULTRAMID A3EG10
80921	1,195	PLASTIC ULTRAMID A3EG5
80922	1,195	PLASTIC ULTRAMID A3EG6
80923	1,195	PLASTIC ULTRAMID A3EG7
80924	1,195	PLASTIC ULTRAMID A3G10
80925	1,196	PLASTIC ULTRAMID A3GA
80926	1,195	PLASTIC ULTRAMID A3G6
80927	1,196	PLASTIC ULTRAMID A3G7
80928	1,196	PLASTIC ULTRAMID A3HG5
80929	1,196	PLASTIC ULTRAMID A3K
80930	1,196	PLASTIC ULTRAMID A3KN
80931	1,196	PLASTIC ULTRAMID A3R
80932	1,196	PLASTIC ULTRAMID A3SK
80933	1,196	PLASTIC ULTRAMID A3W
80934	1,196	PLASTIC ULTRAMID A3WG10
80935	1,196	PLASTIC ULTRAMID A3WG5
80936	1,196	PLASTIC ULTRAMID A3WG6
80937	1,196	PLASTIC ULTRAMID A3WG7
80938	1,195	PLASTIC ULTRAMID A3 X 1G5
80939	1,195	PLASTIC ULTRAMID A3 X 1G7
80940	1,195	PLASTIC ULTRAMID A3 X G5
80941	1,195	PLASTIC ULTRAMID A3 X G7
80942	1,196	PLASTIC ULTRAMID A4
80943	1,196	PLASTIC ULTRAMID A4H
80944	1,197	PLASTIC ULTRAMID A4K
80945	1,197	PLASTIC ULTRAMID A5
80946	1,197	PLASTIC ULTRAMID B3
80947	1,197	PLASTIC ULTRAMID B35
80948	1,197	PLASTIC ULTRAMID B35G3
80949	1,197	PLASTIC ULTRAMID B35SK
80950	1,197	PLASTIC ULTRAMID B35W
80951	1,197	PLASTIC ULTRAMID B3EG10
80952	1,197	PLASTIC ULTRAMID B3EG5
80953	1,197	PLASTIC ULTRAMID B3EG6
80954	1,197	PLASTIC ULTRAMID B3EG7
80955	1,197	PLASTIC ULTRAMID B3G10
80956	1,197	PLASTIC ULTRAMID B3G5
80957	1,197	PLASTIC ULTRAMID B3G5HS
80958	1,198	PLASTIC ULTRAMID B3G6
80959	1,198	PLASTIC ULTRAMID B3G6HS
80960	1,198	PLASTIC ULTRAMID B3G7
80961	1,198	PLASTIC ULTRAMID B3G7HS
80962	1,198	PLASTIC ULTRAMID B3K
80963	1,198	PLASTIC ULTRAMID B3L
80964	1,198	PLASTIC ULTRAMID B3S
80965	1,198	PLASTIC ULTRAMID B3WG10
80966	1,198	PLASTIC ULTRAMID B3WG5
80967	1,198	PLASTIC ULTRAMID B3WG6
80968	1,198	PLASTIC ULTRAMID B3WG7
80969	1,198	PLASTIC ULTRAMID B4
80970	1,198	PLASTIC ULTRAMID B4K
80971	1,198	PLASTIC ULTRAMID B5
80972	1,199	PLASTIC ULTRAMID B5W
80973	1,199	PLASTIC ULTRAMID KR1421
80974	1,199	PLASTIC ULTRAMID KR4600
80975	1,259	POTTING COMPOUND STYCAST 2651/C9 TOX RATE STUDY
80976	541	FILM KYNAR NATURAL TOX RATE STUDY
80977	1,348	RUBBER SILICONE RTV 560 TOX RATE STUDY
80978	958	PLASTIC LEXAN 9600 NATURAL POLYCARBONATE TOX RATE STUDY
80979	318	COATING 828-310 FLAT BLACK TOX RATE STUDY
80980	693	LAMIN EPOXY/GLASS CE9010/7781 TOX RATE STUDY
80981	732	LUBE DRY MOLYKOTE 33 TOX RATE STUDY
80982	1,260	POTTING COMPOUND STYCAST 2850GT/24LV TOX RATE STUDY
80983	308	COATING 03-GY-62 FLAT LIGHT GRAY TOX RATE STUDY
80984	768	MOLD COMPOUND FS10 DAP TOX RATE STUDY
80985	1,257	POTTING COMPOUND SCOTCHCAST EC243EPX TOX RATE STUDY
80986	1,346	RUBBER SILICONE RTV 3140 TOX RATE STUDY
80987	1,349	RUBBER SILICONE RTV 577 TOX RATE STUDY
80988	1,199	PLASTIC ULTRAMID KR4601

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006789 T

MATCD	PAGE	DESIGNATION
80989	1,199	PLASTIC ULTRAMID KR4442/300
80990	1,199	PLASTIC ULTRAMID S3
80991	1,199	PLASTIC ULTRAMID S3K
80992	1,199	PLASTIC ULTRAMID S4
80993	1,226	PLASTIC VINIDUR SZ6415
80994	1,226	PLASTIC VINIDUR SZ6415/VINOFLEX S6815
80995	1,226	PLASTIC VINOFLEX S6115
80996	1,226	PLASTIC VINOFLEX S6815
80997	1,285	RUBBER ESTANE 58013
80998	1,285	RUBBER ESTANE 58110
80999	1,286	RUBBER ESTANE 58600
81000	1,286	RUBBER ESTANE 58610
81001	213	ADHESIVE PLASTILOCK 637
81004	831	PLASTIC BMC100
81005	831	PLASTIC BMC1000
81006	831	PLASTIC BMC102
81007	832	PLASTIC BMC200
81008	832	PLASTIC BMC300
81009	832	PLASTIC BMC400
81010	832	PLASTIC BMC404
81011	832	PLASTIC BMC500
81012	832	PLASTIC BMC700
81013	832	PLASTIC BMC800
81014	832	PLASTIC BMC900
81015	832	PLASTIC BMC902
81016	853	PLASTIC CYCOLAC AR
81017	853	PLASTIC CYCOLAC DFA-R
81018	853	PLASTIC CYCOLAC DH
81019	853	PLASTIC CYCOLAC EP3510
81020	853	PLASTIC CYCOLAC EPB3570
81021	853	PLASTIC CYCOLAC ETS3540
81022	853	PLASTIC CYCOLAC GSM
81023	853	PLASTIC CYCOLAC HM
81024	853	PLASTIC CYCOLAC KJB
81025	853	PLASTIC CYCOLAC KJM
81026	854	PLASTIC CYCOLAC KJT
81027	854	PLASTIC CYCOLAC KJU
81028	854	PLASTIC CYCOLAC KJW
81029	854	PLASTIC CYCOLAC L
81030	854	PLASTIC CYCOLAC LXB
81031	854	PLASTIC CYCOLAC T
81032	854	PLASTIC CYCOLAC TA
81033	854	PLASTIC CYCOLAC X11
81034	854	PLASTIC CYCOLAC X17
81035	854	PLASTIC CYCOLAC X37
81036	854	PLASTIC CYCOLAC X15
81037	854	PLASTIC CYCOLAC Z48
81038	854	PLASTIC CYCOLAC Z86
81039	854	PLASTIC CYCOLAC ZA2
81040	855	PLASTIC CYCOLAC ZA4
81041	855	PLASTIC CYCOLAC ZA7
81042	855	PLASTIC CYCOLOY EHA
81043	855	PLASTIC CYCOVIN CTB
81044	855	PLASTIC CYCOVIN K20
81045	855	PLASTIC CYCOVIN K29
81046	1,083	PLASTIC PREVEX BIA
81047	1,083	PLASTIC PREVEX BJA
81048	1,083	PLASTIC PREVEX BJB
81049	1,083	PLASTIC PREVEX BJC
81050	1,083	PLASTIC PREVEX BJF
81051	1,083	PLASTIC PREVEX BJU
81052	1,084	PLASTIC PREVEX MPF
81053	1,084	PLASTIC PREVEX MPR
81054	1,084	PLASTIC PREVEX MVF
81055	1,084	PLASTIC PREVEX MVP
81056	1,084	PLASTIC PREVEX P2A
81057	1,084	PLASTIC PREVEX P3A
81058	1,084	PLASTIC PREVEX PMA
81059	1,084	PLASTIC PREVEX PQ1
81060	1,084	PLASTIC PREVEX PQA
81061	1,084	PLASTIC PREVEX V2A
81062	1,084	PLASTIC PREVEX V3A
81063	1,084	PLASTIC PREVEX VF1
81064	1,084	PLASTIC PREVEX VFA
81065	1,085	PLASTIC PREVEX VGA
81066	1,085	PLASTIC PREVEX VJA
81067	1,085	PLASTIC PREVEX VJB
81068	1,085	PLASTIC PREVEX VK1
81069	1,085	PLASTIC PREVEX VKA
81070	1,085	PLASTIC PREVEX VM1
81071	1,085	PLASTIC PREVEX VMA
81072	1,085	PLASTIC PREVEX VQ1
81073	1,085	PLASTIC PREVEX VQA
81074	1,085	PLASTIC PREVEX W20
81075	1,085	PLASTIC PREVEX W30
81076	1,085	PLASTIC PREVEX W40
81077	1,085	PLASTIC PREVEX W50
81078	1,085	PLASTIC PREVEX W70
81079	1,084	PLASTIC PREVEX HC2
81080	335	COATING CHEMGLAZE Z306/PYROLAC 123
81081	331	COATING CHEMGLAZE H322/LESONAL PRIMER
81082	332	COATING CHEMGLAZE L300
81083	331	COATING CHEMGLAZE A276/PYROLAC 123
81084	332	COATING CHEMGLAZE L300/PYROLAC 123
81086	902	PLASTIC ESCORENE 3114G
81087	254	ADHESIVE SUPERBONDER 499
81088	267	ADHESIVE ULTRAVIOLET 352
81089	903	PLASTIC ESCORENE 5141G
81090	267	ADHESIVE ULTRAVIOLET 353
81091	267	ADHESIVE ULTRAVIOLET 354
81092	903	PLASTIC ESCORENE 5164G
81093	842	PLASTIC CHEMLOK 218
81094	900	PLASTIC ES6040
81095	900	PLASTIC ES6060
81096	900	PLASTIC ES6071
81097	904	PLASTIC ESCORENE LD-701
81098	900	PLASTIC ES6072
81099	900	PLASTIC ES6360
81100	904	PLASTIC ESCORENE LD-702
81101	900	PLASTIC ES6461

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
81102	900	PLASTIC ES6477
81103	162	ADHESIVE FELPRO GS1
81104	900	PLASTIC ES666
81105	922	PLASTIC FS8160
81106	922	PLASTIC FS8273
81107	162	ADHESIVE FELPRO GS2
81108	922	PLASTIC FS8273-70
81109	922	PLASTIC FS8476
81110	162	ADHESIVE FELPRO GS3 SEALER
81111	922	PLASTIC FS8490
81112	922	PLASTIC FS8477
81113	162	ADHESIVE FELPRO HPS SEALER
81114	922	PLASTIC FS8575
81115	162	ADHESIVE FELPRO PROLOCK FLANGE SEALANT
81116	162	ADHESIVE FELPRO PROLOCK PIPE SEALANT
81117	841	PLASTIC CHEMLOK 210
81118	163	ADHESIVE FIBER RESIN 7010FR
81119	51	ADHESIVE BLACK MAGIC
81120	71	ADHESIVE CHERABOND 18
81121	117	ADHESIVE EP11C
81122	117	ADHESIVE EP12
81123	117	ADHESIVE EP13
81124	967	PLASTIC LUBRICOMP FPF1000
81125	170	ADHESIVE FR14/NO.5 HARDENER
81126	117	ADHESIVE EP21
81127	170	ADHESIVE FR14/NO.6 HARDENER
81128	117	ADHESIVE EP21AO
81129	118	ADHESIVE EP21CLV
81130	118	ADHESIVE EP21D
81131	118	ADHESIVE EP21HV
81132	118	ADHESIVE EP21LP
81133	118	ADHESIVE EP21LV
81134	118	ADHESIVE EP21N
81135	118	ADHESIVE EP22
81136	118	ADHESIVE EP23
81137	118	ADHESIVE EP24
81138	947	PLASTIC IPC5800
81139	118	ADHESIVE EP25
81140	947	PLASTIC IPC6000
81141	118	ADHESIVE EP26
81142	947	PLASTIC IPC6025
81143	118	ADHESIVE EP28
81144	947	PLASTIC IPC6045
81145	118	ADHESIVE EP28M
81146	118	ADHESIVE EP3
81147	119	ADHESIVE EP30
81148	119	ADHESIVE EP30C
81149	119	ADHESIVE EP30D7
81150	119	ADHESIVE EP30DP4X2
81152	890	PLASTIC EP1200 H130
81153	119	ADHESIVE EP30DP8
81154	119	ADHESIVE EP30DP8LV
81155	890	PLASTIC EP1200 H135
81156	119	ADHESIVE EP30HT
81157	119	ADHESIVE EP30M1
81158	891	PLASTIC EP1200 H300
81159	891	PLASTIC EP1200 H350
81160	891	PLASTIC EP1200 H400
81161	119	ADHESIVE EP30S1
81162	891	PLASTIC EP1200 H500
81163	120	ADHESIVE EP33
81164	891	PLASTIC EP1200 H600
81165	120	ADHESIVE EP33CLV
81166	120	ADHESIVE EP33LV
81167	891	PLASTIC EP1200 H650
81168	120	ADHESIVE EP34
81169	891	PLASTIC EP1200 H670
81170	120	ADHESIVE EP34LV
81171	120	ADHESIVE EP35
81172	890	PLASTIC EP1200 H150
81173	890	PLASTIC EP1200 H100
81174	120	ADHESIVE EP35CLV
81175	121	ADHESIVE EP3AO
81176	121	ADHESIVE EP3HTFLM4
81177	121	ADHESIVE EP3HTND
81178	121	ADHESIVE EP3T
81179	121	ADHESIVE EP4
81180	890	PLASTIC EP1200 H170
81181	890	PLASTIC EP1200 H180
81182	121	ADHESIVE EP45
81183	121	ADHESIVE EP45N
81184	891	PLASTIC EP1200 H190
81185	121	ADHESIVE EP5
81186	121	ADHESIVE EP51
81187	891	PLASTIC EP1205
81188	121	ADHESIVE EP51FL
81189	891	PLASTIC EP1210 H300
81190	121	ADHESIVE EP51HT
81191	891	PLASTIC EP1220 H300
81192	122	ADHESIVE EP51M
81193	122	ADHESIVE EP51T
81194	122	ADHESIVE EP62
81195	122	ADHESIVE EP62M
81196	122	ADHESIVE EP72
81197	122	ADHESIVE EP72AO
81198	891	PLASTIC EP1215 H300
81199	122	ADHESIVE EP72M3
81200	122	ADHESIVE EP73
81201	122	ADHESIVE EP74
81202	122	ADHESIVE EP75
81203	891	PLASTIC EP1230 H300
81204	122	ADHESIVE EP76
81205	891	PLASTIC EP1240 H300
81206	122	ADHESIVE EP76M
81207	122	ADHESIVE EP76M1
81208	892	PLASTIC EP1251 H300
81209	122	ADHESIVE EP76M1A
81210	892	PLASTIC EP1255 H300
81211	892	PLASTIC EP1260 H300
81212	123	ADHESIVE EP76M1R

MSFC-HDBK-527 REV F 9999942 0006791 8

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
81213	123	ADHESIVE EP76MF
81214	892	PLASTIC EP1400
81215	892	PLASTIC EP1400 H100
81216	123	ADHESIVE EP76MHP
81217	123	ADHESIVE EP76MHT
81218	892	PLASTIC EP1400 H300
81219	123	ADHESIVE EP76MHTHP
81220	892	PLASTIC EP1470 H100
81221	123	ADHESIVE EP77
81222	123	ADHESIVE EP77M
81223	892	PLASTIC EP1470 H300
81224	123	ADHESIVE EP77M1
81225	892	PLASTIC EP1505 A/B
81226	123	ADHESIVE EP77M1HP
81227	892	PLASTIC EP1525 A/B
81228	892	PLASTIC EP1548 A/B
81229	123	ADHESIVE EP77MF
81230	123	ADHESIVE EP8
81231	892	PLASTIC EP1561 A/B
81232	123	ADHESIVE EP9
81233	192	ADHESIVE MB302
81234	892	PLASTIC EP1562 A/B
81235	192	ADHESIVE MB303
81236	892	PLASTIC EP1800 A/B
81237	255	ADHESIVE SUPREME 10
81238	255	ADHESIVE SUPREME 10S1
81239	893	PLASTIC EP4200 H100
81240	255	ADHESIVE SUPREME 10G
81241	893	PLASTIC EP4200 H300
81242	255	ADHESIVE SUPREME 10HT
81243	893	PLASTIC EP4213
81244	255	ADHESIVE SUPREME 10HT N
81245	255	ADHESIVE SUPREME 10HT NHP
81246	893	PLASTIC EP8200/AB
81247	255	ADHESIVE SUPREME 10TI
81248	893	PLASTIC EP8260 H190
81249	255	ADHESIVE SUPREME 11
81250	893	PLASTIC EP8260 H350
81251	255	ADHESIVE SUPREME 11HT
81252	255	ADHESIVE SUPREME 3HT
81253	255	ADHESIVE SUPREME 3T
81254	274	ADHESIVE UV5PSA
81255	180	ADHESIVE L-M CERAMIC FLOOR
81256	195	ADHESIVE MERECO XLN442
81257	888	PLASTIC EMI-X DA30
81258	200	ADHESIVE MIRACLE CLEAR SEALANT
81259	888	PLASTIC EMI-X DA35
81260	888	PLASTIC EMI-X DA40
81261	200	ADHESIVE MIRACLE D618
81262	888	PLASTIC EMI-X DC1008
81263	202	ADHESIVE MIRACLE SCS100
81264	1,007	PLASTIC NOVATEC-L FL00
81265	1,006	PLASTIC NOVATEC-L F101A
81266	888	PLASTIC EMI-X EC1008
81267	1,007	PLASTIC NOVATEC-L F121
81268	1,007	PLASTIC NOVATEC-L F131
81269	888	PLASTIC EMI-X IC1008
81270	888	PLASTIC EMI-X MA40
81271	888	PLASTIC EMI-X OC100-10
81272	888	PLASTIC EMI-X PC100-10
81273	888	PLASTIC EMI-X PC1008
81274	888	PLASTIC EMI-X QC100-10
81275	1,007	PLASTIC NOVATEC-L F141
81276	1,007	PLASTIC NOVATEC-L F155
81277	1,007	PLASTIC NOVATEC-L F161
81278	888	PLASTIC EMI-X QC1008
81279	1,007	PLASTIC NOVATEC-L F250
81280	888	PLASTIC EMI-X RA30
81281	1,007	PLASTIC NOVATEC-L F261
81282	1,007	PLASTIC NOVATEC-L L300
81283	889	PLASTIC EMI-X RA35
81284	889	PLASTIC EMI-X RA40
81285	1,007	PLASTIC NOVATEC-L L320
81286	889	PLASTIC EMI-X RC100-10
81287	889	PLASTIC EMI-X RC100-12
81288	1,007	PLASTIC NOVATEC-L L330
81289	889	PLASTIC EMI-X RC1008
81290	1,007	PLASTIC NOVATEC-L M400
81291	1,007	PLASTIC NOVATEC-L M420
81292	889	PLASTIC EMI-X WA40
81293	1,007	PLASTIC NOVATEC-L M430
81294	889	PLASTIC EMI-X WC1008
81295	1,008	PLASTIC NOVATEC-L M450
81296	889	PLASTIC EMI-X ZC1008
81297	1,008	PLASTIC NOVATEC-L M460
81298	909	PLASTIC FLUOROMELT FPCC1004
81299	998	PLASTIC NOBLEN BC1
81300	998	PLASTIC NOBLEN BC2
81301	909	PLASTIC FLUOROMELT FPCF1004
81302	909	PLASTIC FLUOROMELT FPCF1006
81303	909	PLASTIC FLUOROMELT FPCLF4024
81304	998	PLASTIC NOBLEN BC2A
81305	998	PLASTIC NOBLEN BC3
81306	909	PLASTIC FLUOROMELT FPCL4020
81307	998	PLASTIC NOBLEN BC3B
81308	909	PLASTIC FLUOROMELT FPEC1004
81309	998	PLASTIC NOBLEN BC4
81310	909	PLASTIC FLUOROMELT FPEC1006
81311	998	PLASTIC NOBLEN BC4C
81312	998	PLASTIC NOBLEN BC5C
81313	909	PLASTIC FLUOROMELT FPEF1004
81314	998	PLASTIC NOBLEN BC6
81315	909	PLASTIC FLUOROMELT FPEF1006
81316	998	PLASTIC NOBLEN BC8
81317	909	PLASTIC FLUOROMELT FPEEL4024
81318	998	PLASTIC NOBLEN BC8B
81319	998	PLASTIC NOBLEN BC8C
81320	909	PLASTIC FLUOROMELT FPEL4060
81321	999	PLASTIC NOBLEN EC8
81322	909	PLASTIC FLUOROMELT FPFC1003

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
81323	999	PLASTIC NOBLEN EC9
81324	999	PLASTIC NOBLEN EC9B
81325	910	PLASTIC FLUOROMELT FPFF1004
81326	999	PLASTIC NOBLEN EX6
81327	999	PLASTIC NOBLEN GX20J
81328	910	PLASTIC FLUOROMELT FPFF1004M
81329	999	PLASTIC NOBLEN JF40M
81330	910	PLASTIC FLUOROMELT FPFL4020
81331	999	PLASTIC NOBLEN JL20
81332	999	PLASTIC NOBLEN MA2
81333	910	PLASTIC FLUOROMELT FPPC1003
81334	999	PLASTIC NOBLEN MA3
81335	999	PLASTIC NOBLEN MA3N
81336	910	PLASTIC FLUOROMELT FPPCL4024
81337	999	PLASTIC NOBLEN MA4
81338	910	PLASTIC FLUOROMELT FPPF1004
81339	999	PLASTIC NOBLEN MA7
81340	910	PLASTIC FLUOROMELT FPPF1004M
81341	910	PLASTIC FLUOROMELT FPPL4020
81342	999	PLASTIC NOBLEN MA8
81343	910	PLASTIC FLUOROMELT FPVC1003
81344	999	PLASTIC NOBLEN MG3B
81345	910	PLASTIC FLUOROMELT FPVCL4024
81346	910	PLASTIC FLUOROMELT FPVM2550
81347	910	PLASTIC FLUOROMELT FPVM3830
81348	1,000	PLASTIC NOBLEN MH4
81349	910	PLASTIC FLUOROMELT FPVM3850
81350	1,000	PLASTIC NOBLEN MH6
81351	922	PLASTIC FULTON 404
81352	1,000	PLASTIC NOBLEN MH8
81353	1,000	PLASTIC NOBLEN MK3G
81354	1,000	PLASTIC NOBLEN MK3H
81355	1,000	PLASTIC NOBLEN MX3A
81356	1,000	PLASTIC NOBLEN X1A
81357	961	PLASTIC LNPD1000
81358	1,000	PLASTIC NOBLEN X1B
81359	961	PLASTIC LNPDA1004
81360	1,236	PLASTIC YUKALON AH-40
81361	1,236	PLASTIC YUKALON EC-51B
81362	1,236	PLASTIC YUKALON EC-70
81363	1,236	PLASTIC YUKALON EH-30
81364	1,236	PLASTIC YUKALON HE-30
81365	1,237	PLASTIC YUKALON HE-40
81366	1,237	PLASTIC YUKALON HE-60
81367	1,237	PLASTIC YUKALON LK-30
81368	962	PLASTIC LNPKL4410
81369	962	PLASTIC LNPKL4610
81370	962	PLASTIC LNPO1000
81371	962	PLASTIC LNPOFA1004
81372	962	PLASTIC LNPOFA1008
81373	962	PLASTIC LNPP1000
81374	962	PLASTIC LNPPA6
81375	962	PLASTIC LNPPA 6/10
81376	962	PLASTIC LNPPA 6/6
81377	1,237	PLASTIC YUKALON LK-50
81378	1,237	PLASTIC YUKALON LM-30
81379	962	PLASTIC LNPPA1002
81380	1,237	PLASTIC YUKALON LM-31
81381	962	PLASTIC LNPPA1004
81382	1,237	PLASTIC YUKALON LM-40
81383	1,237	PLASTIC YUKALON LS-30
81384	1,237	PLASTIC YUKALON MS-30
81385	1,237	PLASTIC YUKALON MT-30
81386	1,237	PLASTIC YUKALON MV-30
81387	1,237	PLASTIC YUKALON NF40
81388	1,237	PLASTIC YUKALON NH-50
81389	962	PLASTIC LNPR1000
81390	1,237	PLASTIC YUKALON YF-30
81391	1,238	PLASTIC YUKALON YK-30
81392	962	PLASTIC LNPR5000
81393	1,238	PLASTIC YUKALON YK-50
81394	1,238	PLASTIC YUKALON YK-60
81395	962	PLASTIC LNPRA1002
81396	1,238	PLASTIC YUKALON YM-61
81397	1,238	PLASTIC YUKALON ZC-30
81398	1,238	PLASTIC YUKALON ZC-52
81399	963	PLASTIC LNPRA1004
81400	963	PLASTIC LNPRAL4023
81401	1,238	PLASTIC YUKALON ZE-41
81402	963	PLASTIC LNPRCL4536
81403	1,238	PLASTIC YUKALON ZE-61
81404	1,238	PLASTIC YUKALON ZF-30
81405	963	PLASTIC LNPRCL4736
81406	963	PLASTIC LNPRE5006
81407	1,238	PLASTIC YUKALON ZF-50
81408	1,238	PLASTIC YUKALON ZF-51
81409	1,238	PLASTIC YUKALON ZF-52
81410	963	PLASTIC LNPREL4536
81411	1,238	PLASTIC YUKALON ZF-53
81412	963	PLASTIC LNPREL4736LW
81413	834	PLASTIC CADON 112
81415	834	PLASTIC CADON 127
81416	834	PLASTIC CADON 135PG
81417	963	PLASTIC LNPRL4610
81418	834	PLASTIC CADON 140
81419	834	PLASTIC CADON 160
81420	834	PLASTIC CADON 161
81421	834	PLASTIC CADON FRX
81422	834	PLASTIC CADON 2100
81423	835	PLASTIC CADON G1606
81424	835	PLASTIC CADON G2110
81425	835	PLASTIC CADON G2120
81426	979	PLASTIC LUSTRAN ABS1148
81427	979	PLASTIC LUSTRAN ABS248
81428	979	PLASTIC LUSTRAN ABS448
81429	979	PLASTIC LUSTRAN ABS648
81430	979	PLASTIC LUSTRAN ABS743
81431	963	PLASTIC LNPRL4620
81432	896	PLASTIC EPSL199
81433	896	PLASTIC EPSL201

MSFC-HDBK-527 REV F 9999942 0006793 1

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
81434	896	PLASTIC EPSL202
81435	896	PLASTIC EPSL203
81436	1,147	PLASTIC TENITE BUTYRATE FORMULA H COMPRESSION
81437	1,147	PLASTIC TENITE BUTYRATE FORMULA H3 COMPRESSION
81438	1,148	PLASTIC TENITE POLYETHYLENE 1572
81439	1,150	PLASTIC TENITE POLYPROPYLENE
81440	1,150	PLASTIC TENITE POLYPROPYLENE 422D
81441	1,062	PLASTIC POLYPROPYLENE 4231A
81442	1,150	PLASTIC TENITE POLYPROPYLENE 4231E
81443	1,150	PLASTIC TENITE POLYPROPYLENE 4232A
81444	1,150	PLASTIC TENITE POLYPROPYLENE 4240
81445	1,151	PLASTIC TENITE POLYPROPYLENE 425A
81446	1,151	PLASTIC TENITE POLYPROPYLENE 4250E
81447	1,152	PLASTIC TENITE POLYPROPYLENE 5250G
81448	1,151	PLASTIC TENITE POLYPROPYLENE 4J31
81449	1,151	PLASTIC TENITE POLYPROPYLENE 4J32
81450	1,152	PLASTIC TENITE POLYPROPYLENE 4M40A
81451	1,153	PLASTIC TENITE PROPIONATE 338 FLOW H6 COMPRESSION
81452	1,153	PLASTIC TENITE PROPIONATE 338 FLOW H6 INJECTION
81453	1,153	PLASTIC TENITE PROPIONATE 350 FLOW H3 COMPRESSION
81454	1,153	PLASTIC TENITE PROPIONATE 350 FLOW H3 INJECTION
81455	1,153	PLASTIC TENITE PROPIONATE 358 FLOW H COMPRESSION
81456	1,153	PLASTIC TENITE PROPIONATE 358 FLOW H INJECTION
81457	1,098	PLASTIC REXENE PE147
81458	1,098	PLASTIC REXENE PP11520V
81459	1,098	PLASTIC REXENE PP14S2A
81460	1,098	PLASTIC REXENE PP31SA
81461	927	PLASTIC GRILAMID L20G
81462	928	PLASTIC GRILAMID L20W20
81463	928	PLASTIC GRILAMID L20W40
81464	928	PLASTIC GRILAMID L25
81465	928	PLASTIC GRILAMID L25W40
81466	928	PLASTIC GRILAMID LKN5H
81467	928	PLASTIC GRILAMID LV3H
81468	929	PLASTIC GRILON A23G NAT 6165
81469	929	PLASTIC GRILON A23GM
81470	929	PLASTIC GRILON A28GM
81471	929	PLASTIC GRILON F40
81472	929	PLASTIC GRILON F47
81473	929	PLASTIC GRILON F50
81474	930	PLASTIC GRILON R40
81475	930	PLASTIC GRILON R40GM
81476	50	ADHESIVE BETASEAL 20-601
81477	50	ADHESIVE BETASEAL 550.02
81478	50	ADHESIVE BETASEAL 553.02
81479	50	ADHESIVE BETASEAL 551.02
81480	50	ADHESIVE BETASEAL XPO1543C
81481	1,286	RUBBER EYPEL F4001
81482	1,286	RUBBER EYPEL F6504
81483	1,287	RUBBER EYPEL F7001
81484	1,287	RUBBER EYPEL F7003
81485	1,287	RUBBER EYPEL F7005
81486	1,287	RUBBER EYPEL F7509
81487	1,287	RUBBER EYPEL F8003
81488	1,287	RUBBER EYPEL F9003
81489	159	ADHESIVE EUCO PLASTISEAL
81490	159	ADHESIVE EUCO POLYSULFIDE SEALANT
81491	1,294	RUBBER JAMAK 7176
81492	900	PLASTIC ESCORENE
81493	901	PLASTIC ESCORENE 1044
81494	873	PLASTIC E20328
81495	873	PLASTIC E2171 8X60
81496	873	PLASTIC E2171 8X61
81497	873	PLASTIC E2171 8X65
81498	873	PLASTIC E260H
81499	874	PLASTIC E261H
81500	874	PLASTIC E264H
81501	874	PLASTIC E2748-9641CB
81502	874	PLASTIC E7300
81503	874	PLASTIC E8353
81504	875	PLASTIC E8354
81505	875	PLASTIC E8354-19189
81506	875	PLASTIC E8379
81507	875	PLASTIC E8382
81508	875	PLASTIC E8411
81509	875	PLASTIC E8414
81510	875	PLASTIC E8625
81511	875	PLASTIC E8636
81512	911	PLASTIC FM10365
81513	911	PLASTIC FM1303-8880
81514	911	PLASTIC FM16771
81515	911	PLASTIC FM21288
81516	911	PLASTIC FM3000
81517	911	PLASTIC FM3001
81518	911	PLASTIC FM3002
81519	911	PLASTIC FM32168
81520	911	PLASTIC FM32175
81521	911	PLASTIC FM32780
81522	911	PLASTIC FM3510
81523	911	PLASTIC FM4002
81524	911	PLASTIC FM4004
81525	912	PLASTIC FM4005F
81526	911	PLASTIC FM4005 X 4648
81527	912	PLASTIC FM4007
81528	912	PLASTIC FM4009
81529	912	PLASTIC FM4011
81530	912	PLASTIC FM4024
81531	912	PLASTIC FM4029F
81532	912	PLASTIC FM4036
81533	912	PLASTIC FM4055
81534	912	PLASTIC FM4056
81535	912	PLASTIC FM4060
81536	912	PLASTIC FM4070
81537	912	PLASTIC FM4555
81538	912	PLASTIC FM50501
81539	912	PLASTIC FM5064
81540	913	PLASTIC FM5085
81541	913	PLASTIC FM510
81542	913	PLASTIC FM5367
81543	913	PLASTIC FM6030

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006794 3

MATCD	PAGE	DESIGNATION
81544	913	PLASTIC FM8130E
81545	1,092	PLASTIC PS1400
81546	1,092	PLASTIC PS2124
81547	1,023	PLASTIC OS 2824
81548	1,092	PLASTIC PS3654
81549	1,092	PLASTIC PS3824
81550	1,092	PLASTIC PS4154
81551	1,092	PLASTIC PS4324
81552	1,092	PLASTIC PS4600
81553	1,092	PLASTIC PS5400
81554	963	PLASTIC LNPW1000
81555	1,092	PLASTIC PS8120
81556	963	PLASTIC LNPWA1004
81557	1,093	PLASTIC PS9524
81558	1,091	PLASTIC PS MX7100A
81559	964	PLASTIC LUBRICOMP A1000
81560	829	PLASTIC BAYBLEND
81561	964	PLASTIC LUBRICOMP AL4030
81562	829	PLASTIC BAYBLEND DP2-1439
81563	829	PLASTIC BAYBLEND DP2-1440
81564	829	PLASTIC BAYBLEND DP2-1441
81565	964	PLASTIC LUBRICOMP AL4410
81566	829	PLASTIC BAYBLEND DP2-1482
81567	964	PLASTIC LUBRICOMP B1000
81568	829	PLASTIC BAYBLEND DP2-1483
81569	829	PLASTIC BAYBLEND DP2-1484
81570	964	PLASTIC LUBRICOMP BBL4326
81571	830	PLASTIC BAYBLEND MC2500
81572	964	PLASTIC LUBRICOMP BFL4036
81573	830	PLASTIC BAYBLEND MC3200
81574	830	PLASTIC BAYBLEND MH6570
81575	964	PLASTIC LUBRICOMP BFL4536
81576	830	PLASTIC BAYBLEND MH6580
81577	964	PLASTIC LUBRICOMP BL4030
81578	830	PLASTIC BAYBLEND MH6595
81579	830	PLASTIC BAYBLEND MJ2500
81580	830	PLASTIC BAYBLEND UT1018
81581	964	PLASTIC LUBRICOMP BL4410
81582	965	PLASTIC LUBRICOMP BL4530
81583	986	PLASTIC MERLON 1143
81584	965	PLASTIC LUBRICOMP C1000
81585	986	PLASTIC MERLON 2407
81586	986	PLASTIC MERLON 2458
81587	965	PLASTIC LUBRICOMP CL4030
81588	965	PLASTIC LUBRICOMP CL4410
81589	986	PLASTIC MERLON 5V-6485
81590	965	PLASTIC LUBRICOMP D1000
81591	965	PLASTIC LUBRICOMP DC1006
81592	965	PLASTIC LUBRICOMP DF1006
81593	965	PLASTIC LUBRICOMP DFL4034
81594	986	PLASTIC MERLON 6355
81595	986	PLASTIC MERLON 6455
81596	986	PLASTIC MERLON 6655
81597	965	PLASTIC LUBRICOMP DFL4038
81598	986	PLASTIC MERLON 6680
81599	965	PLASTIC LUBRICOMP DFL4536
81600	986	PLASTIC MERLON 9415
81601	965	PLASTIC LUBRICOMP DL4010
81602	986	PLASTIC MERLON AL400 1068 TINT
81603	965	PLASTIC LUBRICOMP DL4040
81604	965	PLASTIC LUBRICOMP DL4530
81605	965	PLASTIC LUBRICOMP F1000
81606	986	PLASTIC MERLON FCR-2405
81607	966	PLASTIC LUBRICOMP FL4040
81608	987	PLASTIC MERLON FCR-6255
81609	966	PLASTIC LUBRICOMP FPC1000
81610	987	PLASTIC MERLON HMS 3318
81611	966	PLASTIC LUBRICOMP FPC1003
81612	987	PLASTIC MERLON M39 (L)
81613	966	PLASTIC LUBRICOMP FPCF1004M
81614	987	PLASTIC MERLON M40 (H)
81615	966	PLASTIC LUBRICOMP FPCF1005
81616	987	PLASTIC MERLON M40 (L)
81617	966	PLASTIC LUBRICOMP FPE1000
81618	987	PLASTIC MERLON M50 (L)
81619	987	PLASTIC MERLON M50 (H)
81620	966	PLASTIC LUBRICOMP FPEC1003
81621	987	PLASTIC MERLON RX3 1113 TINT
81622	966	PLASTIC LUBRICOMP FPEC1006
81623	966	PLASTIC LUBRICOMP FPEF1002
81624	987	PLASTIC MERLON SF-600 0.25 INCHES
81625	966	PLASTIC LUBRICOMP FPEF1003
81626	966	PLASTIC LUBRICOMP FPEF1004
81627	987	PLASTIC MERLON SF-800 0.25 INCHES
81628	987	PLASTIC MERLON SF-810 0.25 INCHES
81629	987	PLASTIC MERLON SF-820 0.24 INCHES
81630	966	PLASTIC LUBRICOMP FPEF1004M
81631	987	PLASTIC MERLON T-85
81632	966	PLASTIC LUBRICOMP FPEF1005
81633	987	PLASTIC MERLON T-95
81634	967	PLASTIC LUBRICOMP FPEF1006
81635	1,016	PLASTIC NYDUR BC 303
81636	1,016	PLASTIC NYDUR BC 402
81637	967	PLASTIC LUBRICOMP FPEFL4035
81638	1,016	PLASTIC NYDUR BKV 130
81639	1,017	PLASTIC NYDUR BKV 140
81640	967	PLASTIC LUBRICOMP FPEL4060
81641	1,034	PLASTIC PETLON 3530
81642	967	PLASTIC LUBRICOMP FPEL4210
81643	967	PLASTIC LUBRICOMP FPEL4320
81644	1,034	PLASTIC PETLON 4530
81645	1,034	PLASTIC PETLON 7530
81646	1,051	PLASTIC POCAN B1505
81647	1,051	PLASTIC POCAN B3225
81648	1,051	PLASTIC POCAN B3235
81649	1,052	PLASTIC POCAN B4225
81650	1,052	PLASTIC POCAN B4235
81651	1,052	PLASTIC POCAN S1506
81652	913	PLASTIC FM8720
81653	913	PLASTIC FM9294

MSFC-HDBK-527 REV F 9999942 0006795 5

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
81654	980	PLASTIC M2014
81655	980	PLASTIC M2037
81656	980	PLASTIC M6204
81657	1,041	PLASTIC PI730
81658	1,041	PLASTIC PI740
81659	1,041	PLASTIC PI745
81660	1,041	PLASTIC PI750
81661	1,116	PLASTIC S660
81662	1,116	PLASTIC S680
81663	1,116	PLASTIC S690
81664	1,116	PLASTIC S695
81665	1,116	PLASTIC S706
81666	1,116	PLASTIC S706M
81667	1,117	PLASTIC SI9002
81668	1,117	PLASTIC SI9041
81669	1,224	PLASTIC VE49595
81670	1,235	PLASTIC X28057
81671	1,312	RUBBER PNF 240-001
81672	1,312	RUBBER PNF 225-001
81673	1,312	RUBBER PNF 260-004
81674	1,312	RUBBER PNF 265-003
81675	1,312	RUBBER PNF 265-004
81676	1,312	RUBBER PNF 270-001
81677	1,313	RUBBER PNF 270-003
81678	1,313	RUBBER PNF 275-006
81679	1,313	RUBBER PNF 275-009
81680	1,313	RUBBER PNF 280-003
81681	1,313	RUBBER PNF 280-008
81682	1,313	RUBBER PNF 280-009
81683	1,313	RUBBER PNF 285-005
81684	1,313	RUBBER PNF 290-003
81685	910	PLASTIC FLUOROTEMP 103
81686	949	PLASTIC KEL-F CTFE CRYSTLLINE
81687	170	ADHESIVE FOMO 5-10
81688	174	ADHESIVE HANDIFOAM
81689	174	ADHESIVE HANDIFOAM 2
81690	35	ADHESIVE AR1005
81691	35	ADHESIVE AR1009
81692	35	ADHESIVE AR1150
81693	36	ADHESIVE AR1776
81694	36	ADHESIVE AR1930FR
81695	79	ADHESIVE CR3125
81696	897	PLASTIC ER2020
81697	897	PLASTIC ER2023
81698	897	PLASTIC ER2027
81699	897	PLASTIC ER2028
81700	897	PLASTIC ER2036
81701	898	PLASTIC ER3042
81702	897	PLASTIC ER2047
81703	898	PLASTIC ER2205
81704	898	PLASTIC ER2220
81705	898	PLASTIC ER2300
81706	898	PLASTIC ER2380
81707	898	PLASTIC ER2381
81708	898	PLASTIC ER2400
81709	220	ADHESIVE POLYTECH 4000
81710	220	ADHESIVE POLYTECH 4020
81711	220	ADHESIVE POLYTECH 4140
81712	220	ADHESIVE POLYTECH 4150
81713	1,123	PLASTIC STYPOL 047-1000
81714	1,123	PLASTIC STYPOL 047-1050
81715	1,125	PLASTIC STYPOL 40-2780
81716	1,126	PLASTIC STYPOL 40-3925 43% GLASS
81717	1,126	PLASTIC STYPOL 40-3925 50% GLASS
81718	1,127	PLASTIC STYPOL 40-7116
81719	1,128	PLASTIC STYPOL 42-2640
81720	1,128	PLASTIC STYPOL 42-2675
81721	23	ADHESIVE ACCUTHANE UR1100
81722	162	ADHESIVE FD4207
81723	230	ADHESIVE RESIWELD FE0004
81724	230	ADHESIVE RESIWELD FE0185
81725	230	ADHESIVE RESIWELD FE1402
81726	230	ADHESIVE RESIWELD FE5050
81727	230	ADHESIVE RESIWELD FE6721
81728	230	ADHESIVE RESIWELD FE7005
81729	233	ADHESIVE SC2505
81730	272	ADHESIVE UR2139
81731	272	ADHESIVE UR2170
81732	272	ADHESIVE UR2183
81733	893	PLASTIC EPOCAST 11B/9812
81734	894	PLASTIC EPOCAST 31B/9216
81735	894	PLASTIC EPOCAST 31D/9216
81736	894	PLASTIC EPOCAST 31D/927
81737	894	PLASTIC EPOCAST 32 A/B
81738	894	PLASTIC EPOCAST 417
81739	894	PLASTIC EPOCAST 420
81740	894	PLASTIC EPOCAST 432
81741	894	PLASTIC EPOCAST 442
81742	894	PLASTIC EPOCAST 443
81743	894	PLASTIC EPOCAST 452
81744	894	PLASTIC EPOCAST 460
81745	894	PLASTIC EPOCAST 461
81746	894	PLASTIC EPOCAST 471
81747	894	PLASTIC EPOCAST 475
81748	895	PLASTIC EPOCAST 4B A/9816
81749	895	PLASTIC EPOCAST 4D A/951
81750	895	PLASTIC EPOCAST 4D A/9633
81751	895	PLASTIC EPOCAST 50 A/9449
81752	895	PLASTIC EPOCAST 50 A/946
81753	895	PLASTIC EPOCAST 50 A/9816
81754	895	PLASTIC EPOCAST 9 A/B
81755	1,367	RUBBER URALANE 1440 A/B
81756	1,367	RUBBER URALANE 1460 A/B
81757	1,367	RUBBER URALANE 87645 A/B
81758	1,367	RUBBER URALANE 87647 A/B
81759	955	PLASTIC LEXAN 141L
81760	955	PLASTIC LEXAN 1500
81761	955	PLASTIC LEXAN 151
81762	955	PLASTIC LEXAN 153
81763	955	PLASTIC LEXAN 154

MSFC-HDBK-527 REV F 9999942 0006796 7

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
81764	955	PLASTIC LEXAN 161
81765	955	PLASTIC LEXAN 181
81766	956	PLASTIC LEXAN 503
81767	959	PLASTIC LEXAN BE1
81768	959	PLASTIC LEXAN HF1110
81769	960	PLASTIC LEXAN HF1130
81770	960	PLASTIC LEXAN HF2110
81771	960	PLASTIC LEXAN HF2130
81772	960	PLASTIC LEXAN HP1
81773	960	PLASTIC LEXAN HP2
81774	960	PLASTIC LEXAN HP3
81775	960	PLASTIC LEXAN HP4
81776	960	PLASTIC LEXAN HP5
81777	961	PLASTIC LEXAN OQ1
81778	961	PLASTIC LEXAN PPC4501
81779	961	PLASTIC LEXAN PPC4701
81780	961	PLASTIC LEXAN WR2210
81781	1,003	PLASTIC NORYL 1222
81782	1,003	PLASTIC NORYL 1390
81783	1,003	PLASTIC NORYL 1391
81784	1,003	PLASTIC NORYL 722
81785	1,003	PLASTIC NORYL 844
81786	1,004	PLASTIC NORYL 888
81787	1,004	PLASTIC NORYL EN185
81788	1,004	PLASTIC NORYL EN212
81789	1,004	PLASTIC NORYL GTX 810
81790	1,004	PLASTIC NORYL GTX 820
81791	1,004	PLASTIC NORYL GTX 830
81792	1,004	PLASTIC NORYL GTX 910
81793	1,005	PLASTIC NORYL PLUS CRN410
81794	1,005	PLASTIC NORYL PLUS CRN639
81795	1,005	PLASTIC NORYL PLUS RNF420
81796	1,005	PLASTIC NORYL PLUS RNF430
81797	1,005	PLASTIC NORYL PLUS SPN410
81798	1,005	PLASTIC NORYL PLUS SPN420
81799	1,005	PLASTIC NORYL PLUS SPN422L
81800	1,005	PLASTIC NORYL PLUS SPN580
81801	1,005	PLASTIC NORYL PLUS SPN585H
81802	1,005	PLASTIC NORYL PLUS UVN580
81803	1,006	PLASTIC NORYL SE1/GFN2
81804	1,006	PLASTIC NORYL SE1/GFN3
81805	1,222	PLASTIC VALOX 357
81806	1,222	PLASTIC VALOX 730
81807	1,223	PLASTIC VALOX 736
81808	170	ADHESIVE G623
81809	170	ADHESIVE G624
81810	170	ADHESIVE G627
81811	170	ADHESIVE G635
81812	170	ADHESIVE G641
81813	171	ADHESIVE G662
81814	171	ADHESIVE G687
81815	171	ADHESIVE G697
81816	1,316	RUBBER RTV 12C
81817	1,316	RUBBER RTV 12W
81818	231	ADHESIVE RTV 41
81819	1,316	RUBBER RTV 511
81820	1,316	RUBBER RTV 6157
81821	1,316	RUBBER RTV 627
81822	1,316	RUBBER RTV 660
81823	1,316	RUBBER RTV 662
81824	1,316	RUBBER RTV 668
81825	1,316	RUBBER RTV 670
81826	1,316	RUBBER RTV 700 BETA 1
81827	1,317	RUBBER RTV 700 BETA 2
81828	1,317	RUBBER RTV 700 BETA 4
81829	1,317	RUBBER RTV 700 BETA 5
81830	1,317	RUBBER RTV 8262
81831	1,317	RUBBER SE5559U
81832	927	PLASTIC GLASROD HIR
81833	927	PLASTIC GLASROD MTS
81834	927	PLASTIC GLASROD SG200
81835	927	PLASTIC GLASTIC GPO3
81836	171	ADHESIVE GC1100
81837	171	ADHESIVE GC1500 CLASS A
81838	171	ADHESIVE GC1500 CLASS B
81839	171	ADHESIVE GC1900
81840	171	ADHESIVE GC200 CLASS A
81841	1,346	RUBBER SILICONE RTV 3140 UNCURED
81842	171	ADHESIVE GC200 CLASS B
81843	1,294	RUBBER GC202 CLASS B
81844	172	ADHESIVE GC3007
81845	172	ADHESIVE GC401 CLASS A
81846	172	ADHESIVE GC401 CLASS B
81847	172	ADHESIVE GC401LD CLASS A
81848	172	ADHESIVE GC401LD CLASS B
81849	172	ADHESIVE GC402
81850	172	ADHESIVE GC407 CLASS A
81851	172	ADHESIVE GC407 CLASS B
81852	172	ADHESIVE GC408 CLASS A
81853	172	ADHESIVE GC408 CLASS B
81854	172	ADHESIVE GC409 CLASS B
81855	172	ADHESIVE GC414 CLASS B2
81856	172	ADHESIVE GC435
81857	172	ADHESIVE GC450 CLASS A
81858	173	ADHESIVE GC450 CLASS B
81859	173	ADHESIVE GC450 CLASS C
81860	173	ADHESIVE GCL455 CLASS B
81861	173	ADHESIVE GC502
81862	173	ADHESIVE GC92
81863	211	ADHESIVE PL410
81864	211	ADHESIVE PL420
81865	211	ADHESIVE PL425 EPOXY
81866	1,285	RUBBER ESTANE 58092
81867	1,285	RUBBER ESTANE 58122
81868	1,285	RUBBER ESTANE 58130
81869	1,285	RUBBER ESTANE 58133
81870	1,285	RUBBER ESTANE 58134
81871	1,285	RUBBER ESTANE 58137
81872	1,285	RUBBER ESTANE 58206
81873	1,285	RUBBER ESTANE 58271

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006797 9 ■

MATCD	PAGE	DESIGNATION
81874	1,286	RUBBER ESTANE 58277
81875	1,286	RUBBER ESTANE 58309
81876	1,286	RUBBER ESTANE 58311
81877	1,286	RUBBER ESTANE 58360
81878	1,286	RUBBER ESTANE 58370
81879	1,286	RUBBER ESTANE 58630
81880	1,286	RUBBER ESTANE 58810
81881	1,286	RUBBER ESTANE 58863
81882	1,286	RUBBER ESTANE 58881
81883	1,286	RUBBER ESTANE 58887
81884	842	PLASTIC CLEARSTUF 8002
81885	932	PLASTIC GTC160
81886	842	PLASTIC CHEMTROL PP TYPE 1
81887	989	PLASTIC MICARTA 213
81888	989	PLASTIC MICARTA 219
81889	989	PLASTIC MICARTA 221
81890	989	PLASTIC MICARTA 223
81891	989	PLASTIC MICARTA 238
81892	989	PLASTIC MICARTA 254
81893	989	PLASTIC MICARTA 259-2
81894	990	PLASTIC MICARTA 262
81895	990	PLASTIC MICARTA 281
81896	990	PLASTIC MICARTA 286
81897	990	PLASTIC MICARTA 400
81898	990	PLASTIC MICARTA 423
81899	990	PLASTIC MICARTA 429
81900	990	PLASTIC MICARTA 431
81901	990	PLASTIC MICARTA 496
81902	990	PLASTIC MICARTA 51F33
81903	990	PLASTIC MICARTA 51F60
81904	990	PLASTIC MICARTA 51P77
81905	990	PLASTIC MICARTA 51P88
81906	991	PLASTIC MICARTA H12426
81907	991	PLASTIC MICARTA H17825
81908	967	PLASTIC LUBRICOMP FPFC1003
81909	967	PLASTIC LUBRICOMP FPFF1003M
81910	967	PLASTIC LUBRICOMP FPFF1004M
81911	967	PLASTIC LUBRICOMP FPP1000
81912	967	PLASTIC LUBRICOMP FPFC1003PC
81913	1,231	PLASTIC WELLAMID 42LN-N
81914	967	PLASTIC LUBRICOMP FPPF1004
81915	967	PLASTIC LUBRICOMP FPPF1004M
81916	1,231	PLASTIC WELLAMID 42LH-XE-N
81917	967	PLASTIC LUBRICOMP FPPML3312
81918	1,231	PLASTIC WELLAMID 42HI11-XE-N
81919	968	PLASTIC LUBRICOMP FPV1000
81920	1,231	PLASTIC WELLAMID 42LN-2-N
81921	968	PLASTIC LUBRICOMP FPVC1003
81922	1,231	PLASTIC WELLAMID 42LN-2-XE-N
81923	1,231	PLASTIC WELLAMID FR22F-N
81924	1,231	PLASTIC WELLAMID FR64-NRD
81925	1,231	PLASTIC WELLAMID FRGF25-66-N
81926	1,231	PLASTIC WELLAMID FRGS25-66-N
81927	968	PLASTIC LUBRICOMP FPVCL4024
81928	1,232	PLASTIC WELLAMID GF13-60-42LH-N
81929	968	PLASTIC LUBRICOMP FPVM2550
81930	1,232	PLASTIC WELLAMID GF13-66-22LH-N
81931	968	PLASTIC LUBRICOMP FPVM3850
81932	968	PLASTIC LUBRICOMP FULTON 404D
81933	1,232	PLASTIC WELLAMID GF13-66 X3-N
81934	968	PLASTIC LUBRICOMP FULTON 441
81935	1,232	PLASTIC WELLAMID GF30-60 42LH-N
81936	1,232	PLASTIC WELLAMID GF30-60 XE-N
81937	968	PLASTIC LUBRICOMP FULTON 441D
81938	968	PLASTIC LUBRICOMP G1000
81939	1,232	PLASTIC WELLAMID GF33-66 22LH-N
81940	968	PLASTIC LUBRICOMP GC1006
81941	1,232	PLASTIC WELLAMID GF33-66 XE-N
81942	968	PLASTIC LUBRICOMP GF1006
81943	1,232	PLASTIC WELLAMID GF33-66 XE-N1
81944	968	PLASTIC LUBRICOMP GFL4022
81945	1,232	PLASTIC WELLAMID GR43-66 XE-N1
81946	968	PLASTIC LUBRICOMP GFL4036
81947	1,232	PLASTIC WELLAMID GFT13-66 XE-N
81948	968	PLASTIC LUBRICOMP GL4030
81949	1,232	PLASTIC WELLAMID GS25-66 22L-N
81950	969	PLASTIC LUBRICOMP GL4520
81951	1,232	PLASTIC WELLAMID GS25-66 LH-N
81952	969	PLASTIC LUBRICOMP GML4334
81953	1,232	PLASTIC WELLAMID GS40-60 42L-N
81954	969	PLASTIC LUBRICOMP H1000
81955	969	PLASTIC LUBRICOMP HFL4325
81956	969	PLASTIC LUBRICOMP I1000
81957	1,233	PLASTIC WELLAMID GS40-60 42LH-N
81958	969	PLASTIC LUBRICOMP IC1006
81959	1,232	PLASTIC WELLAMID GS40-60 22L-N
81960	969	PLASTIC LUBRICOMP IF1006
81961	1,233	PLASTIC WELLAMID GSF25/15-66 22L-N
81962	1,233	PLASTIC WELLAMID MR409 22H-N
81963	969	PLASTIC LUBRICOMP IFL4036
81964	969	PLASTIC LUBRICOMP IFL4536
81965	1,233	PLASTIC WELLAMID MR259 22LH-N
81966	969	PLASTIC LUBRICOMP IL4040
81967	969	PLASTIC LUBRICOMP IL4410
81968	969	PLASTIC LUBRICOMP IL4530
81969	966	PLASTIC LUBRICOMP FJL4036
81970	969	PLASTIC LUBRICOMP JL4030
81971	1,233	PLASTIC WELLAMID MR410 22H-N
81972	969	PLASTIC LUBRICOMP K1000
81973	970	PLASTIC LUBRICOMP KC1004
81974	1,233	PLASTIC WELLAMID MRGF25/15 22H-N
81975	970	PLASTIC LUBRICOMP KF1006
81976	1,233	PLASTIC WELLAMID MRGF25/15 42H-N
81977	970	PLASTIC LUBRICOMP KFL4036
81978	1,233	PLASTIC WELLAMID MRGF30/10 42H-N
81979	266	ADHESIVE TUFFBOND
81980	266	ADHESIVE TUFFBOND QUIK SET
81981	991	PLASTIC MICARTA H17900
81982	991	PLASTIC MICARTA H18331
81983	991	PLASTIC MICARTA H18332

MSFC-HDBK-527 REV F 9999942 0006798 0

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
81984	991	PLASTIC MICARTA H18333
81985	991	PLASTIC MICARTA H18720
81986	992	PLASTIC MICARTA H19128
81987	992	PLASTIC MICARTA H19242
81988	992	PLASTIC MICARTA H19243
81989	992	PLASTIC MICARTA H22033
81990	992	PLASTIC MICARTA H23655
81991	992	PLASTIC MICARTA H23842
81992	992	PLASTIC MICARTA H24721
81993	992	PLASTIC MICARTA H24907
81994	992	PLASTIC MICARTA H25126
81995	992	PLASTIC MICARTA H25219
81996	992	PLASTIC MICARTA H26000
81997	992	PLASTIC MICARTA H2898
81998	992	PLASTIC MICARTA H5639
81999	991	PLASTIC MICARTA H09454
82000	992	PLASTIC MICARTA H6-1348
82001	1,062	PLASTIC POLYPROPYLENE 20% CALCIUM CARBONATE FILLED
82002	1,062	PLASTIC POLYPROPYLENE 20% TALC FILLED
82003	1,062	PLASTIC POLYPROPYLENE 40% CALCIUM CARBONATE FILLED
82004	1,062	PLASTIC POLYPROPYLENE 40% TALC FILLED
82005	933	PLASTIC HAYSITE 12000
82006	933	PLASTIC HAYSITE 13600
82007	933	PLASTIC HAYSITE 14100
82008	933	PLASTIC HAYSITE 16100
82009	933	PLASTIC HAYSITE 16600
82010	933	PLASTIC HAYSITE 17000
82011	933	PLASTIC HAYSITE 18500
82012	933	PLASTIC HAYSITE 20000
82013	933	PLASTIC HAYSITE 270 FR2
82014	933	PLASTIC HAYSITE 30000
82015	933	PLASTIC HAYSITE 40000
82016	933	PLASTIC HAYSITE 42000
82017	933	PLASTIC HAYSITE 43000
82018	933	PLASTIC HAYSITE 44000
82019	934	PLASTIC HAYSITE 46000
82020	934	PLASTIC HAYSITE 47000
82021	934	PLASTIC HAYSITE 48000
82022	934	PLASTIC HAYSITE 53000
82023	934	PLASTIC HAYSITE 60000
82024	934	PLASTIC HAYSITE 70000
82025	1,367	RUBBER URALITE 3121S
82026	1,367	RUBBER URALITE 3130
82027	1,367	RUBBER URALITE 3136
82028	1,367	RUBBER URALITE 3138
82029	1,367	RUBBER URALITE 3140
82030	1,367	RUBBER URALITE 3142
82031	1,367	RUBBER URALITE 3148
82032	1,368	RUBBER URALITE 3150
82033	1,368	RUBBER URALITE 3154
82034	895	PLASTIC EPOLITE 3300
82035	895	PLASTIC EPOLITE 3301
82036	895	PLASTIC EPOLITE 3302
82037	895	PLASTIC EPOLITE 3306
82038	895	PLASTIC EPOLITE 3306-1
82039	895	PLASTIC EPOLITE 3354
82040	895	PLASTIC EPOLITE 3362
82041	1,086	PLASTIC PROFAX 6323
82042	1,086	PLASTIC PROFAX 6331
82043	1,086	PLASTIC PROFAX 6331NW
82044	1,086	PLASTIC PROFAX 6523
82045	1,086	PLASTIC PROFAX 6524
82046	1,086	PLASTIC PROFAX 65F4-2
82047	1,086	PLASTIC PROFAX 65F4-4
82048	1,086	PLASTIC PROFAX 65F5-2
82049	1,086	PLASTIC PROFAX 65F5-4
82050	1,086	PLASTIC PROFAX 6723
82051	1,086	PLASTIC PROFAX 6823
82052	1,086	PLASTIC PROFAX 7523
82053	1,086	PLASTIC PROFAX 75F4-2
82054	1,086	PLASTIC PROFAX 75F4-4
82055	1,087	PLASTIC PROFAX 75F5-2
82056	1,087	PLASTIC PROFAX 75F5-4
82057	1,087	PLASTIC PROFAX 7623
82058	1,087	PLASTIC PROFAX 7624
82059	1,087	PLASTIC PROFAX 7723
82060	1,087	PLASTIC PROFAX 7823
82061	1,087	PLASTIC PROFAX 8523
82062	1,087	PLASTIC PROFAX 8623
82063	1,087	PLASTIC PROFAX PD064
82064	1,087	PLASTIC PROFAX PD195
82065	1,087	PLASTIC PROFAX SB222PM
82066	943	PLASTIC HUNTSMAN 201
82067	943	PLASTIC HUNTSMAN 202
82068	943	PLASTIC HUNTSMAN 203
82069	943	PLASTIC HUNTSMAN 206
82070	943	PLASTIC HUNTSMAN 208
82071	943	PLASTIC HUNTSMAN 210
82072	943	PLASTIC HUNTSMAN AH703
82073	943	PLASTIC HUNTSMAN AH721M
82074	943	PLASTIC HUNTSMAN AH731
82075	944	PLASTIC HUNTSMAN DP351HF
82076	943	PLASTIC HUNTSMAN DP3037
82077	944	PLASTIC HUNTSMAN DP355
82078	944	PLASTIC HUNTSMAN HCC201
82079	944	PLASTIC HUNTSMAN HCC208
82080	944	PLASTIC HUNTSMAN HCC271
82081	944	PLASTIC HUNTSMAN HCC360
82082	944	PLASTIC HUNTSMAN HCC50
82083	944	PLASTIC HUNTSMAN HCC702
82084	944	PLASTIC HUNTSMAN HCC705
82085	944	PLASTIC HUNTSMAN HCC707
82086	944	PLASTIC HUNTSMAN HCC730
82087	944	PLASTIC HUNTSMAN HCC760
82088	944	PLASTIC HUNTSMAN HCC765
82089	944	PLASTIC HUNTSMAN HCC779
82090	945	PLASTIC HUNTSMAN HCC817
82091	945	PLASTIC HUNTSMAN HCC840
82092	945	PLASTIC HUNTSMAN HCC850
82093	945	PLASTIC HUNTSMAN HCC851

MSFC-HDBK-527 REV F 9999942 0006799 2

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
82094	945	PLASTIC HUNTSMAN PS331
82095	945	PLASTIC HUNTSMAN PS338
82096	945	PLASTIC HUNTSMAN PS345
82097	945	PLASTIC HUNTSMAN PS312
82098	945	PLASTIC HUNTSMAN PS314
82099	945	PLASTIC HUNTSMAN PS316
82100	945	PLASTIC HUNTSMAN PS318
82101	945	PLASTIC HUNTSMAN PS333
82102	945	PLASTIC HUNTSMAN PS335
82103	945	PLASTIC HUNTSMAN PS350
82104	946	PLASTIC HUNTSMAN PS351
82105	946	PLASTIC HUNTSMAN SEP15
82106	57	ADHESIVE BRUTEM 91
82107	58	ADHESIVE BRUTEM 92
82108	798	PLASTIC 1D30HIF
82109	798	PLASTIC 1D40
82110	798	PLASTIC 1D50
82111	801	PLASTIC 2S30
82112	802	PLASTIC 3D36
82113	861	PLASTIC DIELECTRITE 44-0
82114	861	PLASTIC DIELECTRITE 44-1 BMC
82115	861	PLASTIC DIELECTRITE 44-10 BMC
82116	861	PLASTIC DIELECTRITE 44-10 HG
82117	861	PLASTIC DIELECTRITE 44-10 HG-C
82118	861	PLASTIC DIELECTRITE 44-22 BMC
82119	861	PLASTIC DIELECTRITE 44 DR-UL BMC
82120	861	PLASTIC DIELECTRITE 46-09 BMC
82121	861	PLASTIC DIELECTRITE 46-12 BMC
82122	861	PLASTIC DIELECTRITE 46-14
82123	861	PLASTIC DIELECTRITE 46-16 BMC
82124	861	PLASTIC DIELECTRITE 46-3 BMC
82125	861	PLASTIC DIELECTRITE 48-50 BMC
82126	862	PLASTIC DIELECTRITE 48-56 BMC
82127	874	PLASTIC E7052
82128	874	PLASTIC E7074
82129	888	PLASTIC EM7302
82130	946	PLASTIC INSULSTRUC P1001FR BMC
82131	946	PLASTIC INSULSTRUC P5000GP
82132	946	PLASTIC INSULSTRUC P5003FR
82133	980	PLASTIC M4135
82134	1,055	PLASTIC POLYDAP 6120
82135	1,056	PLASTIC POLYDAP 6120F
82136	1,056	PLASTIC POLYDAP 6130
82137	1,056	PLASTIC POLYDAP 6130F
82138	1,056	PLASTIC POLYDAP 6160
82139	1,056	PLASTIC POLYDAP 6220
82140	1,056	PLASTIC POLYDAP 6260
82141	947	PLASTIC IPCPX6000
82142	948	PLASTIC IPCPX6030
82143	948	PLASTIC IPCRCF3020
82144	948	PLASTIC IPCRCF3030
82145	948	PLASTIC IPCRCF3040
82146	948	PLASTIC IPCRX171E
82147	948	PLASTIC IPCRX173
82148	948	PLASTIC IPCRX176
82149	948	PLASTIC IPCRX1834
82150	948	PLASTIC IPCRX5308
82151	946	PLASTIC IPC104
82152	946	PLASTIC IPC120
82153	946	PLASTIC IPC170
82154	946	PLASTIC IPC171E
82155	946	PLASTIC IPC173
82156	946	PLASTIC IPC176
82157	946	PLASTIC IPC1832
82158	946	PLASTIC IPC1833
82159	947	PLASTIC IPC1834
82160	947	PLASTIC IPC1836
82161	947	PLASTIC IPC1837
82162	947	PLASTIC IPC5007
82163	947	PLASTIC IPC5100
82164	947	PLASTIC IPC5303
82165	947	PLASTIC IPC5304
82166	947	PLASTIC IPC5306
82167	947	PLASTIC IPC5308
82168	1,064	PLASTIC POLYSAR 520
82169	1,064	PLASTIC POLYSAR 5220
82170	1,064	PLASTIC POLYSAR 525
82171	1,064	PLASTIC POLYSAR 555
82172	1,064	PLASTIC POLYSAR 777
82173	1,064	PLASTIC POLYSAR 9720
82174	1,078	PLASTIC PREMIGLAS 1000 BMC GLASS
82175	1,078	PLASTIC PREMIGLAS 1100 BMC LS 15% GLASS
82176	1,078	PLASTIC PREMIGLAS 1100 BMC-LS 22% GLASS
82177	1,078	PLASTIC PREMIGLAS 1100 BMC-LS 30%GLAS
82178	1,078	PLASTIC PREMIGLAS 1100-05
82179	1,078	PLASTIC PREMIGLAS 1100-10
82180	1,078	PLASTIC PREMIGLAS 1100-15
82181	1,078	PLASTIC PREMIGLAS 1200 SMC-LS 15% GLASS
82182	1,078	PLASTIC PREMIGLAS 1200 SMC-LS 22% GLASS
82183	1,078	PLASTIC PREMIGLAS 1200 SMC-LS 30% GLASS
82184	1,078	PLASTIC PREMIGLAS 2000 BMC 10% GLASS
82185	1,079	PLASTIC PREMIGLAS 2000 BMC 15% GLASS
82186	1,079	PLASTIC PREMIGLAS 2000 BMC 22% GLASS
82187	1,079	PLASTIC PREMIGLAS 2000 BMC 30% GLASS
82188	1,079	PLASTIC PREMIGLAS 2003 BMC 10% GLASS
82189	1,079	PLASTIC PREMIGLAS 2003 BMC 15% GLASS
82190	1,079	PLASTIC PREMIGLAS 2003 22% GLASS
82191	1,079	PLASTIC PREMIGLAS 2003 BMC 30% GLASS
82192	1,079	PLASTIC PREMIGLAS 2100 BMC-LS 15% GLASS
82193	1,079	PLASTIC PREMIGLAS 2100 BMC-LS 22% GLASS
82194	1,079	PLASTIC PREMIGLAS 2100 BMC-LS 30% GLASS
82195	1,079	PLASTIC PREMIGLAS 2103 BMC-LS 15% GLASS
82196	1,079	PLASTIC PREMIGLAS 2103 BMC-LS 22% GLASS
82197	1,079	PLASTIC PREMIGLAS 2103 BMC-LS 30% GLASS
82198	1,079	PLASTIC PREMIGLAS 2200 SMC-LS 15% GLASS
82199	1,079	PLASTIC PREMIGLAS 2200 SMC-LS 22% GLASS
82200	1,080	PLASTIC PREMIGLAS 2200 SMC-LS 30% GLASS
82201	1,080	PLASTIC PREMIGLAS 2203 SMC-LS 15% GLASS
82202	1,080	PLASTIC PREMIGLAS 2203 SMC-LS 22% GLASS
82203	1,080	PLASTIC PREMIGLAS 2203 SMC-LS 30% GLASS

MSFC-HDBK-527 REV F 9999942 0006800 5

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
82204	1,080	PLASTIC PREMIGLAS 3000 BMC 15% GLASS
82205	1,080	PLASTIC PREMIGLAS 3000 BMC 30% GLASS
82206	1,080	PLASTIC PREMIGLAS 3100 BMC-LS 15% GLASS
82207	1,080	PLASTIC PREMIGLAS 3100 BMC-LS 22% GLASS
82208	1,080	PLASTIC PREMIGLAS 3100 BMC-LS 30% GLASS
82209	1,080	PLASTIC PREMIGLAS 3140 MSG
82210	1,080	PLASTIC PREMIGLAS 3200 SMC-LS 15% GLASS
82211	1,080	PLASTIC PREMIGLAS 3200 SMC-LS 22% GLASS
82212	1,080	PLASTIC PREMIGLAS 3200 SMC-LS 30% GLASS
82213	1,080	PLASTIC PREMIGLAS 4000 BMC 15% GLASS
82214	1,081	PLASTIC PREMIGLAS 4000 BMC 22% GLASS
82215	1,081	PLASTIC PREMIGLAS 4000 BMC 30% GLASS
82216	1,081	PLASTIC PREMIGLAS 4100 BMC-LS 22% GLASS
82217	1,081	PLASTIC PREMIGLAS 4100 BMC-LS 30% GLASS
82218	1,081	PLASTIC PREMIGLAS 4200 SMC-LS 15% GLASS
82219	1,081	PLASTIC PREMIGLAS 4200 SMC-LS 22% GLASS
82220	1,081	PLASTIC PREMIGLAS 4200 SMC-LS 30% GLASS
82221	1,081	PLASTIC PREMIGLAS 7100 BMC 15% GLASS
82222	1,081	PLASTIC PREMIGLAS 7100 BMC 22% GLASS
82223	1,081	PLASTIC PREMIGLAS 7200 SMC
82224	1,081	PLASTIC PREMIGLAS 7200 SMC 15% GLASS
82225	1,081	PLASTIC PREMIGLAS 7200 SMC 22% GLASS
82226	1,081	PLASTIC PREMIGLAS 7200 SMC 30% GLASS
82227	1,081	PLASTIC PREMIGLAS 8140 TMC
82228	1,082	PLASTIC PREMIGLAS 8200 SMC
82229	1,082	PLASTIC PREMIGLAS BMC-EMI
82230	1,082	PLASTIC PREMIGLAS BMC-ESD
82231	1,082	PLASTIC PREMIGLAS EPOXY 1200E 50% GLASS
82232	1,082	PLASTIC PREMIGLAS EPOXY 1200E 65% GLASS
82233	1,082	PLASTIC PREMIGLAS HSMC
82234	1,082	PLASTIC PREMIGLAS HSMC 3200 50% GLASS
82235	1,082	PLASTIC PREMIGLAS SMC-EMI
82236	1,082	PLASTIC PREMIGLAS SMC-ESD
82237	1,082	PLASTIC PREMIGLAS TMC-EMI
82238	1,082	PLASTIC PREMIGLAS TWC-ESD
82239	1,082	PLASTIC PREMIJECT 1100V BMC-LS
82240	1,082	PLASTIC PREMIJECT 1140 TMC-LS
82241	1,082	PLASTIC PREMIJECT 1140V TMC-LS
82242	1,083	PLASTIC PREMIJECT 6000 BMC 10% GLASS
82243	1,083	PLASTIC PREMIJECT 6000 BMC 15% GLASS
82244	1,083	PLASTIC PREMIJECT 6000 BMC 20% GLASS
82245	1,083	PLASTIC PREMIJECT 6000 BMC 5% GLASS
82246	1,083	PLASTIC PREMIJECT 6100 BMC-LS 10% GLASS
82247	1,083	PLASTIC PREMIJECT 6100 BMC-LS 15% GLASS
82248	1,083	PLASTIC PREMIJECT 6100 BMC-LS 20% GLASS
82249	1,083	PLASTIC PREMIJECT 6100 BMC-LS 5% GLASS
82250	9	ADHESIVE 444R
82251	11	ADHESIVE 898C
82252	206	ADHESIVE P/S 700
82253	206	ADHESIVE P/S 706A
82254	206	ADHESIVE P/S 706B1/2
82255	206	ADHESIVE P/S 706B2
82256	206	ADHESIVE P/S 714
82257	206	ADHESIVE P/S 870C
82258	206	ADHESIVE P/S 870A1/2
82259	206	ADHESIVE P/S 870A2
82260	206	ADHESIVE P/S 870B1/2
82261	206	ADHESIVE P/S 870C24
82262	206	ADHESIVE P/S 870-2
82263	206	ADHESIVE P/S 870C12
82264	207	ADHESIVE P/S 872B1/2
82265	207	ADHESIVE P/S 872B2
82266	207	ADHESIVE P/S 881-1/6
82267	207	ADHESIVE P/S 888D1/2
82268	207	ADHESIVE P/S 888-2
82269	207	ADHESIVE P/S 890A1/2
82270	207	ADHESIVE P/S 890A2
82271	207	ADHESIVE P/S 890B1/2
82272	207	ADHESIVE P/S 890B4
82273	207	ADHESIVE P/S 898B8
82274	207	ADHESIVE P/S 898D2
82275	207	ADHESIVE P/S 899A1/2
82276	207	ADHESIVE P/S 899A2
82277	207	ADHESIVE P/S 899B1/2
82278	208	ADHESIVE P/S 899B1/4
82279	208	ADHESIVE P/S 899B2
82280	208	ADHESIVE P/S 899B4
82281	208	ADHESIVE P/S 899B6
82282	221	ADHESIVE PR1425B1/2
82283	221	ADHESIVE PR1425B2
82284	223	ADHESIVE PR1725B2
82285	221	ADHESIVE PR1403G A-1/2
82286	221	ADHESIVE PR1403G A-2
82287	221	ADHESIVE PR1403G B-1/2
82288	221	ADHESIVE PR1403G B-2
82289	221	ADHESIVE PR1422A1/2
82290	221	ADHESIVE PR1422A2
82291	221	ADHESIVE PR1422B1/2
82292	221	ADHESIVE PR1422B2
82293	221	ADHESIVE PR1422G B1/2
82294	221	ADHESIVE PR1422G B2
82295	221	ADHESIVE PR1426
82296	222	ADHESIVE PR1431G TI
82297	222	ADHESIVE PR1431G T2
82298	222	ADHESIVE PR1431G T3
82299	222	ADHESIVE PR1431G T4
82300	222	ADHESIVE PR1435
82301	222	ADHESIVE PR1435G
82302	222	ADHESIVE PR1436G A1/2
82303	222	ADHESIVE PR1436G A2
82304	222	ADHESIVE PR1436G B2
82305	222	ADHESIVE PR1436G B4
82306	222	ADHESIVE PR1436G SPRAYABLE
82307	222	ADHESIVE PR1440A1/2
82308	222	ADHESIVE PR1440A2
82309	222	ADHESIVE PR1440B1/2
82310	223	ADHESIVE PR1440B2
82311	223	ADHESIVE PR1440C2
82312	223	ADHESIVE PR1440C20
82313	224	ADHESIVE PR1750A1/2

MSFC-HDBK-527 REV F 9999942 0006801 7

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
82314	223	ADHESIVE PR1750A-2
82315	224	ADHESIVE PR1755
82316	224	ADHESIVE PR702
82317	224	ADHESIVE PR703
82318	224	ADHESIVE PR810
82319	224	ADHESIVE PR812
82320	1,096	PLASTIC RESINOID 1312
82321	1,096	PLASTIC RESINOID 1320
82322	1,096	PLASTIC RESINOID 1321
82323	1,096	PLASTIC RESINOID 1322
82324	1,096	PLASTIC RESINOID 1323
82325	1,096	PLASTIC RESINOID 1324
82326	1,096	PLASTIC RESINOID 1325
82327	1,096	PLASTIC RESINOID 1340
82328	1,097	PLASTIC RESINOID 1360
82329	1,097	PLASTIC RESINOID 1362
82330	1,097	PLASTIC RESINOID 1370
82331	1,097	PLASTIC RESINOID 1401
82332	1,097	PLASTIC RESINOID 1402
82333	1,097	PLASTIC RESINOID 2002-2
82334	1,097	PLASTIC RESINOID 2002-4
82335	1,097	PLASTIC RESINOID 2002-4P
82336	1,097	PLASTIC RESINOID 2002C5
82337	1,241	PLASTICS RESINOID 2010
82338	1,097	PLASTIC RESINOID 2016
82339	1,097	PLASTIC RESINOID 2017
82340	1,097	PLASTIC RESINOID 2018
82341	1,097	PLASTIC RESINOID 7003S
82342	1,097	PLASTIC RESINOID 7005
82343	1,098	PLASTIC RESINOID 7051
82344	1,098	PLASTIC RESINOID 7051SS
82345	1,098	PLASTIC RESINOID 7201
82346	949	PLASTIC KINEL 3515
82347	1,134	PLASTIC TECHNYL A20
82348	1,134	PLASTIC TECHNYL A20 V25
82349	1,134	PLASTIC TECHNYL A216
82350	1,134	PLASTIC TECHNYL A216 V10
82351	1,134	PLASTIC TECHNYL A216 V15
82352	1,135	PLASTIC TECHNYL A216 V20
82353	1,135	PLASTIC TECHNYL A216 V25
82354	1,135	PLASTIC TECHNYL A216 V30
82355	1,135	PLASTIC TECHNYL A216 V35
82356	1,135	PLASTIC TECHNYL A216 V40
82357	1,135	PLASTIC TECHNYL A216 V50
82358	1,135	PLASTIC TECHNYL A217
82359	1,135	PLASTIC TECHNYL A218
82360	1,135	PLASTIC TECHNYL A218 V20
82361	1,135	PLASTIC TECHNYL A218 V25
82362	1,135	PLASTIC TECHNYL A218 V30
82363	1,135	PLASTIC TECHNYL A218 V40
82364	1,135	PLASTIC TECHNYL A221
82365	1,135	PLASTIC TECHNYL A222
82366	1,136	PLASTIC TECHNYL A228 MT40
82367	1,136	PLASTIC TECHNYL A248 MT30
82368	1,136	PLASTIC TECHNYL A319
82369	1,136	PLASTIC TECHNYL B216
82370	1,136	PLASTIC TECHNYL B216 V20
82371	1,241	PLASTICS WELLITE 9000GP
82372	1,241	PLASTICS WELLITE 9320GR
82373	1,241	PLASTICS WELLITE 9330GR
82374	1,241	PLASTICS WELLITE 9730GRVO
82375	1,241	PLASTICS WELLPET FRGF2030
82376	1,241	PLASTICS WELLPET FG1020
82377	1,242	PLASTICS WELLPET GF1030
82378	1,242	PLASTICS WELLPET GF1045
82379	1,061	PLASTIC POLYMETHYLPENTENE DX 845
82380	1,164	PLASTIC THERMALUX UDEL POLYSULFONE
82381	1,225	PLASTIC VICTREX PEEK
82382	1,233	PLASTIC WESTLAKE CELCON/UNFILLED
82383	1,233	PLASTIC WESTLAKE CELCON/25PCT GLASS
82384	1,233	PLASTIC WESTLAKE ETHYLUX
82385	1,233	PLASTIC WESTLAKE LENNITE
82386	1,233	PLASTIC WESTLAKE LENNITE UHMW
82387	1,233	PLASTIC WESTLAKE LENNITE XL
82388	1,234	PLASTIC WESTLAKE NORYL EN-185
82389	1,234	PLASTIC WESTLAKE NORYL SE-1-GFN3
82390	1,234	PLASTIC WESTLAKE POLYMETHYLPENTENE
82391	1,234	PLASTIC WESTLAKE POLYSTYRENE
82392	970	PLASTIC LUBRICOMP KFL4536
82393	1,234	PLASTIC WESTLAKE PROPYLUX
82394	970	PLASTIC LUBRICOMP KL4010
82395	1,234	PLASTIC WESTLAKE STYROLUX
82396	970	PLASTIC LUBRICOMP KL4020
82397	1,234	PLASTIC WESTLAKE VICTREX
82398	970	PLASTIC LUBRICOMP KL4050
82399	970	PLASTIC LUBRICOMP KL4030
82400	1,234	PLASTIC WESTLAKE VICTREX 4101GL30 (30 PCT REINFORCED)
82401	970	PLASTIC LUBRICOMP KL4320
82402	1,234	PLASTIC WESTLAKE ZELUX
82403	970	PLASTIC LUBRICOMP KL4540
82404	970	PLASTIC LUBRICOMP KL4540D
82405	1,234	PLASTIC WESTLAKE ZELUX 10 PCT GLASS REINFORCED
82406	1,234	PLASTIC WESTLAKE ZELUX 20 PCT GLASS REINFORCED
82407	970	PLASTIC LUBRICOMP LCL4033
82408	1,234	PLASTIC WESTLAKE ZELUX 40 PCT GLASS REINFORCED
82409	1,234	PLASTIC WESTLAKE ZELUX W
82410	970	PLASTIC LUBRICOMP LFL4036
82411	1,017	PLASTIC NYLAFIL G-3/30 MS/5
82412	971	PLASTIC LUBRICOMP LL4040
82413	1,017	PLASTIC NYLAFIL G-3/40 MS/5
82414	971	PLASTIC LUBRICOMP M1000
82415	1,017	PLASTIC NYLAFIL J-1/20
82416	971	PLASTIC LUBRICOMP MFL4036 HS
82417	971	PLASTIC LUBRICOMP ML4040 HS
82418	971	PLASTIC LUBRICOMP NYKON P
82419	971	PLASTIC LUBRICOMP NYKON Q
82421	971	PLASTIC LUBRICOMP O1000
82422	971	PLASTIC LUBRICOMP OC1006
82423	971	PLASTIC LUBRICOMP OF1008

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006802 9

MATCD	PAGE	DESIGNATION
82424	971	PLASTIC LUBRICOMP OFL4326
82425	971	PLASTIC LUBRICOMP OFL4536
82426	1,017	PLASTIC NYLAFIL J-3/20
82427	971	PLASTIC LUBRICOMP OL4040
82428	1,017	PLASTIC NYLAFIL POLYCARBAFIL G-50/20
82429	810	PLASTIC ABSAFIL G1200/10
82430	810	PLASTIC ABSAFIL J1200/20
82431	810	PLASTIC ABSAFIL J1200/30
82432	971	PLASTIC LUBRICOMP P1000
82433	972	PLASTIC LUBRICOMP PC1006
82434	972	PLASTIC LUBRICOMP PDX4208
82435	811	PLASTIC ACRYAFIL G40/20/V0
82436	972	PLASTIC LUBRICOMP PDX5156
82437	811	PLASTIC ACRYAFIL G40/30/V0
82438	811	PLASTIC ACRYAFIL G40/35
82439	972	PLASTIC LUBRICOMP PF1006
82440	811	PLASTIC ACRYAFIL G40/20
82441	972	PLASTIC LUBRICOMP PFL4036
82443	972	PLASTIC LUBRICOMP PFL4536
82444	972	PLASTIC LUBRICOMP PL4030
82445	972	PLASTIC LUBRICOMP PL4040
82446	972	PLASTIC LUBRICOMP PL4310
82447	880	PLASTIC ELECTRAFIL 50EC-2
82448	880	PLASTIC ELECTRAFIL 50EC-1
82449	972	PLASTIC LUBRICOMP PL4540
82450	880	PLASTIC ELECTRAFIL 70EC-1
82451	972	PLASTIC LUBRICOMP Q1000
82452	880	PLASTIC ELECTRAFIL 75EC1
82453	880	PLASTIC ELECTRAFIL 75EC3
82454	972	PLASTIC LUBRICOMP QC1006
82455	880	PLASTIC ELECTRAFIL ABS1200 AF40FR
82456	972	PLASTIC LUBRICOMP QF1006
82457	880	PLASTIC ELECTRAFIL G1/SS/5
82458	973	PLASTIC LUBRICOMP QFL4036
82459	880	PLASTIC ELECTRAFIL G100/SS/10
82460	973	PLASTIC LUBRICOMP QFL4536
82461	973	PLASTIC LUBRICOMP QL4040
82462	880	PLASTIC ELECTRAFIL G1700/SS/3/BK5658
82463	973	PLASTIC LUBRICOMP QL4410
82464	880	PLASTIC ELECTRAFIL G3/10/CF/25
82465	973	PLASTIC LUBRICOMP QL4540
82466	881	PLASTIC ELECTRAFIL G50/30/CF/10
82467	973	PLASTIC LUBRICOMP R1000
82468	881	PLASTIC ELECTRAFIL G50/CF/20
82469	881	PLASTIC ELECTRAFIL G50/CF/40
82470	973	PLASTIC LUBRICOMP RC1004
82471	973	PLASTIC LUBRICOMP RC1006
82472	973	PLASTIC LUBRICOMP RC1008
82473	973	PLASTIC LUBRICOMP RF100-10
82474	973	PLASTIC LUBRICOMP RF1002
82475	973	PLASTIC LUBRICOMP RF1004
82476	973	PLASTIC LUBRICOMP RF1006
82477	973	PLASTIC LUBRICOMP RF1008
82478	881	PLASTIC ELECTRAFIL G50/CF/5/SS/5
82479	881	PLASTIC ELECTRAFIL G50/SS/10
82480	881	PLASTIC ELECTRAFIL G50/SS/5/FR
82482	1,136	PLASTIC TECHNYL B216 V30
82483	1,136	PLASTIC TECHNYL B216 V50
82484	1,136	PLASTIC TECHNYL B217
82485	1,136	PLASTIC TECHNYL B218
82486	1,136	PLASTIC TECHNYL B218 MX30
82487	1,136	PLASTIC TECHNYL B218 MX40
82488	1,136	PLASTIC TECHNYL B230
82489	1,136	PLASTIC TECHNYL C216
82490	1,136	PLASTIC TECHNYL C216 V20
82491	1,137	PLASTIC TECHNYL C216 V30
82492	1,137	PLASTIC TECHNYL C316
82493	1,137	PLASTIC TECHNYL D316
82494	1,137	PLASTIC TECHNYL D317
82495	949	PLASTIC KINEL 4515
82496	950	PLASTIC KINEL 5504
82497	950	PLASTIC KINEL 5505
82498	950	PLASTIC KINEL 5508
82499	950	PLASTIC KINEL 5511
82500	950	PLASTIC KINEL 5514
82501	950	PLASTIC KINEL 5517
82502	950	PLASTIC KINEL 5518
82503	1,282	RUBBER EP6923
82504	1,315	RUBBER RM630
82505	889	PLASTIC ENVEX 1315
82506	1,051	PLASTIC PLEXIGLASS G-UVT
82507	1,050	PLASTIC PLEXIGLASS 2-UVT
82508	1,051	PLASTIC PLEXIGLASS MC
82509	1,187	PLASTIC TIFFAK A
82510	1,103	PLASTIC ROTOFLAME RF1001
82511	1,103	PLASTIC ROTOTHENE R2010
82512	1,103	PLASTIC ROTOTHENE R8107U
82513	1,103	PLASTIC ROTOTHENE R835U
82514	1,103	PLASTIC ROTOTHENE R8307U
82515	1,103	PLASTIC ROTOTHENE R8405
82516	1,103	PLASTIC ROTOTHON XP1
82517	893	PLASTIC EPIC RESINS P6001
82518	893	PLASTIC EPIC RESINS P6004
82519	1,093	PLASTIC PWB 14A
82520	1,093	PLASTIC PWB 14A 100% REGIND
82521	1,093	PLASTIC PWB 14A VIRGIN
82522	1,093	PLASTIC PWB 14A VIRGIN WITH 20% REGRIND
82523	1,093	PLASTIC PWB 14A VIRGIN WITH 50% REGRIND
82524	797	PLASTIC 14B
82525	1,094	PLASTIC PWB 14B 100% REGRIND
82526	1,094	PLASTIC PWB 14B VIRGIN
82527	1,094	PLASTIC PWB 14B VIRGIN WITH 20% REGRIND
82528	1,094	PLASTIC PWB 14B VIRGIN WITH 50% REGRIND
82529	1,094	PLASTIC PWB 21A
82530	1,094	PLASTIC PWB 21A 100% REGRIND
82531	1,094	PLASTIC PWB 21A VIRGIN
82532	1,094	PLASTIC PWB 21A VIRGIN WITH 20% REGRIND
82533	1,094	PLASTIC PWB 21A VIRGIN WITH 50% REGRIND
82534	1,094	PLASTIC PWB 21B
82535	798	PLASTIC 21B 100% REGRIND

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006803 0 ■

MATCD	PAGE	DESIGNATION
82536	1,094	PLASTIC PWB 21B VIRGIN
82537	1,094	PLASTIC PWB 21B VIRGIN WITH 20% REGRIND
82538	1,094	PLASTIC PWB 21B VIRGIN WITH 50% REGRIND
82539	1,106	PLASTIC RTP 1000FRA
82540	1,106	PLASTIC RTP 1002FRA
82541	1,106	PLASTIC RTP 1005FR
82542	1,106	PLASTIC RTP 1005FRA
82543	1,106	PLASTIC RTP 101FR
82544	1,106	PLASTIC RTP 103
82545	1,106	PLASTIC RTP 103CC
82546	1,106	PLASTIC RTP 103SP
82547	1,106	PLASTIC RTP 105CC FR
82548	1,106	PLASTIC RTP 1103
82549	1,106	PLASTIC RTP 1105FR
82550	1,315	RUBBER RTP 1203-80D
82551	1,315	RUBBER RTP 1203-90A
82552	1,107	PLASTIC RTP 128
82553	1,315	RUBBER RTP 1299 X 34515B
82554	1,107	PLASTIC RTP 1303
82555	1,106	PLASTIC RTP 1205
82556	1,107	PLASTIC RTP 1378
82557	1,107	PLASTIC RTP 1383
82558	1,107	PLASTIC RTP 1383 TFE 15
82559	1,107	PLASTIC RTP 1385
82560	1,107	PLASTIC RTP 1385 TFE 15
82561	1,107	PLASTIC RTP 1385HEC
82562	1,107	PLASTIC RTP 1387
82563	1,107	PLASTIC RTP 1387HEC
82564	1,107	PLASTIC RTP 1403
82565	1,107	PLASTIC RTP 1405
82566	1,107	PLASTIC RTP 141
82567	1,107	PLASTIC RTP 150
82568	1,315	RUBBER RTP 1503-40D
82569	1,316	RUBBER RTP 1503-55D
82570	1,108	PLASTIC RTP 152
82571	1,108	PLASTIC RTP 199 X 22898
82572	1,108	PLASTIC RTP 199 X 23835
82573	1,109	PLASTIC RTP 199-38016
82574	1,108	PLASTIC RTP 199 X 28017C
82575	1,108	PLASTIC RTP 199 X 50485
82576	1,108	PLASTIC RTP 199 X 50486A
82577	1,108	PLASTIC RTP 199 X 28016
82578	1,108	PLASTIC RTP 199 X 28016 HI1
82579	1,108	PLASTIC RTP 199 X 28016 HI2
82580	1,108	PLASTIC RTP 199 X 28559
82581	1,108	PLASTIC RTP 199 X 50148C
82582	1,108	PLASTIC RTP 199 X 50466A
82583	1,108	PLASTIC RTP 199 X 50466B
82584	1,108	PLASTIC RTP 199 X 50486B
82585	1,109	PLASTIC RTP 199 X 50487B
82586	1,109	PLASTIC RTP 199 X 50487B HI1
82587	1,109	PLASTIC RTP 199 X 50487B HI2
82588	1,109	PLASTIC RTP 199 X 50504
82589	1,109	PLASTIC RTP 199 X 50505
82590	1,109	PLASTIC RTP 200FR
82591	1,109	PLASTIC RTP 200MS
82592	1,109	PLASTIC RTP 200 TFE 20
82593	1,109	PLASTIC RTP 200H FR
82594	1,109	PLASTIC RTP 202FR
82595	1,109	PLASTIC RTP 203
82596	1,109	PLASTIC RTP 203A
82597	1,110	PLASTIC RTP 203D
82598	1,110	PLASTIC RTP 203H
82599	1,109	PLASTIC RTP 203 TFE 20
82600	1,110	PLASTIC RTP 204FR
82601	1,110	PLASTIC RTP 205FR
82602	1,110	PLASTIC RTP 205MS
82603	1,110	PLASTIC RTP 205D FR
82604	1,110	PLASTIC RTP 2105
82605	1,110	PLASTIC RTP 2205
82606	1,110	PLASTIC RTP 225
82607	1,110	PLASTIC RTP 283
82608	1,110	PLASTIC RTP 283 TFE 10
82609	1,110	PLASTIC RTP 285
82610	1,111	PLASTIC RTP 285P
82611	1,110	PLASTIC RTP 285 TFE 15
82612	1,110	PLASTIC RTP 285HEC
82613	1,111	PLASTIC RTP 287
82614	1,111	PLASTIC RTP 287HEC
82615	1,111	PLASTIC RTP 287P
82616	1,111	PLASTIC RTP 299A 27567
82617	1,111	PLASTIC RTP 301FR
82618	1,111	PLASTIC RTP 303
82619	1,111	PLASTIC RTP 303FR
82620	1,111	PLASTIC RTP 303 TFE 10
82621	1,111	PLASTIC RTP 305FR
82622	1,111	PLASTIC RTP 305 TFE 15
82623	1,111	PLASTIC RTP 307FR
82624	1,111	PLASTIC RTP 383
82625	1,112	PLASTIC RTP 383FR
82626	1,111	PLASTIC RTP 383 TFE 20
82627	1,112	PLASTIC RTP 385
82628	1,112	PLASTIC RTP 385 TFE 15
82629	1,112	PLASTIC RTP 385HEC
82630	1,112	PLASTIC RTP 387
82631	1,112	PLASTIC RTP 387HEC
82632	1,112	PLASTIC RTP 403
82633	1,112	PLASTIC RTP 503
82634	1,112	PLASTIC RTP 603
82635	1,113	PLASTIC RTP 783
82636	1,112	PLASTIC RTP 685
82637	1,112	PLASTIC RTP 685HEC
82638	1,112	PLASTIC RTP 687
82639	1,112	PLASTIC RTP 687HEC
82640	1,112	PLASTIC RTP 703
82641	1,113	PLASTIC RTP 799 X 50492
82642	1,113	PLASTIC RTP 800 TFE 20
82643	1,113	PLASTIC RTP 803
82644	1,113	PLASTIC RTP 805 TFE 15
82645	1,113	PLASTIC RTP 885

MSFC-HDBK-527 REV F 9999942 0006804 2

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
82646	1,113	PLASTIC RTP 903
82647	1,113	PLASTIC RTP 905
82648	245	ADHESIVE SHELDAHL T300
82649	133	ADHESIVE EPON 815/V15
82650	133	ADHESIVE EPON 815/V25
82651	134	ADHESIVE EPON 826/1031/EMI24
82652	134	ADHESIVE EPON 826/1031/NMA/EMI24
82653	134	ADHESIVE EPON 826/1031/NMA/PYRADINE
82654	134	ADHESIVE EPON 826/BF3MEA
82655	135	ADHESIVE EPON 826/DADS/BF3MEA
82656	135	ADHESIVE EPON 826/DDS/BF3MEA
82657	135	ADHESIVE EPON 826/HHPA/BDMA
82658	135	ADHESIVE EPON 826/MPDA
82659	135	ADHESIVE EPON 826/MPDA/ANILINE
82660	135	ADHESIVE EPON 826/MTHPA/BDMA
82661	135	ADHESIVE EPON 826/NMA/EMI24
82662	135	ADHESIVE EPON 826/PAPA/BDMA
82663	135	ADHESIVE EPON 826/Y
82664	135	ADHESIVE EPON 828/1031/EMI24
82665	136	ADHESIVE EPON 828/1031/MTHPA/EMI24
82666	136	ADHESIVE EPON 828/1031/Y
82667	136	ADHESIVE EPON 828/871/AEP
82668	142	ADHESIVE EPON/871/DDSA/EMI24
82669	136	ADHESIVE EPON 828/871/MDA
82670	136	ADHESIVE EPON 828/871/NMA/EMI24
82671	142	ADHESIVE EPON 871/PAPA/EMI24
82672	136	ADHESIVE EPON 828/871/Z
82673	136	ADHESIVE EPON 828/872/AEP
82674	11	ADHESIVE 828/872/PAPA/EMI-24
82675	136	ADHESIVE EPON 828/872/Z
82676	136	ADHESIVE EPON 828/AEP
82677	136	ADHESIVE EPON 828/BF3MEA
82678	136	ADHESIVE EPON 828/CA
82679	137	ADHESIVE EPON 828/D
82680	137	ADHESIVE EPON 828/D230
82681	137	ADHESIVE EPON 828/D230/AEP
82682	137	ADHESIVE EPON 828/D400
82683	137	ADHESIVE EPON 828/DADS
82684	137	ADHESIVE EPON 828/DADS/BF3MEA
82685	137	ADHESIVE EPON 828/DDSA/EMI24
82686	137	ADHESIVE EPON 828/DETA
82687	137	ADHESIVE EPON 828/DSA/BDMA
82688	138	ADHESIVE EPON 828/EMI24
82689	138	ADHESIVE EPON 828/EMPOL1040/DMP10
82690	138	ADHESIVE EPON 828/HHPA/BDMA
82691	138	ADHESIVE EPON 828/HHPA/DMP30
82692	139	ADHESIVE EPON 828/HHPA/EMI24
82693	139	ADHESIVE EPON 828/IPD
82694	139	ADHESIVE EPON 828/L ARAMINE C260
82695	139	ADHESIVE EPON 828/LP3/DMP30
82696	139	ADHESIVE EPON 828/MDA
82697	139	ADHESIVE EPON 828/MDA/DMP30
82698	139	ADHESIVE EPON 828/MPDA
82699	139	ADHESIVE EPON 828/MPDA/SILICA FILLER
82700	139	ADHESIVE EPON 828/MTHPA/BDMA
82701	139	ADHESIVE EPON 828/NMA/BDMA
82702	143	ADHESIVE EPON/NMA/EMI-24
82703	139	ADHESIVE EPON 828/PA/BDMA
82704	139	ADHESIVE EPON 828/PACM20
82705	139	ADHESIVE EPON 828/PAPA/BDMA
82706	139	ADHESIVE EPON 828/PAPA/EMI24
82707	140	ADHESIVE EPON 828/PMDA
82708	140	ADHESIVE EPON 828/T1
82709	140	ADHESIVE EPON 828/TETA
82710	140	ADHESIVE EPON 828/THPA/BDMA
82711	140	ADHESIVE EPON 828/THPA/EMI24
82712	140	ADHESIVE EPON 828/V40
82713	141	ADHESIVE EPON 828/Y
82714	141	ADHESIVE EPON 828/ZZLA0822
82715	142	ADHESIVE EPON 834/NMA/DMP30
82716	142	ADHESIVE EPON 834/THPA/DMP30
82717	142	ADHESIVE EPON 872/828/HHPA/DMP30
82718	142	ADHESIVE EPON 872/828/V40
82719	142	ADHESIVE EPON 872/871/AEP
82720	142	ADHESIVE EPON 872/871/AEP/OCTYL AMINE
82721	246	ADHESIVE SIKA 15LM
82722	246	ADHESIVE SIKAFLEX 1A
82723	246	ADHESIVE SIKAFLEX 2C NS/NL
82724	974	PLASTIC LUBRICOMP RFL4036
82725	974	PLASTIC LUBRICOMP RFL4416
82726	881	PLASTIC ELECTRAFIL J1/15/CP/30
82727	881	PLASTIC ELECTRAFIL J1/CF/10
82728	881	PLASTIC ELECTRAFIL J1/CF/15/TF/20
82729	881	PLASTIC ELECTRAFIL J1/CF/20
82730	881	PLASTIC ELECTRAFIL J1/CF/30
82731	881	PLASTIC ELECTRAFIL J1/CF/30/TF/13/SI/2
82732	881	PLASTIC ELECTRAFIL J1/CF/30/TF/15
82733	881	PLASTIC ELECTRAFIL J1/CF/40
82734	882	PLASTIC ELECTRAFIL J1/CF/40/VO/OD5208
82735	882	PLASTIC ELECTRAFIL J1/CF/50
82736	882	PLASTIC ELECTRAFIL J1/CN/15
82737	882	PLASTIC ELECTRAFIL J1/CN/40
82738	882	PLASTIC ELECTRAFIL J1/CP/20
82739	974	PLASTIC LUBRICOMP RFL4536
82740	882	PLASTIC ELECTRAFIL J1/CP/30
82741	882	PLASTIC ELECTRAFIL J1/CP/40
82742	882	PLASTIC ELECTRAFIL J100/CF/30
82743	882	PLASTIC ELECTRAFIL J105/CF/30
82744	882	PLASTIC ELECTRAFIL J1100/CF/30
82745	882	PLASTIC ELECTRAFIL J1105/CF/30
82746	974	PLASTIC LUBRICOMP RFL4616
82747	974	PLASTIC LUBRICOMP RL4010
82748	974	PLASTIC LUBRICOMP RL4040
82749	974	PLASTIC LUBRICOMP RL4040 FR
82750	882	PLASTIC ELECTRAFIL J1106/CF/30
82751	974	PLASTIC LUBRICOMP RL4310
82752	974	PLASTIC LUBRICOMP RL4410
82754	974	PLASTIC LUBRICOMP RL4540
82755	882	PLASTIC ELECTRAFIL J1200/CF/10
82756	882	PLASTIC ELECTRAFIL J1200/CF/20

MSFC-HDBK-527 REV F 9999942 0006805 4

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
82757	974	PLASTIC LUBRICOMP RL4610
82758	974	PLASTIC LUBRICOMP RL4730
82759	883	PLASTIC ELECTRAFIL J1200/SS/7/BK2089
82760	883	PLASTIC ELECTRAFIL J1300/10/CF/5/SS/5
82761	974	PLASTIC LUBRICOMP S1000
82762	883	PLASTIC ELECTRAFIL J1300/CF/15/CP/15
82763	883	PLASTIC ELECTRAFIL J1300/CF/20
82764	975	PLASTIC LUBRICOMP SFL4036
82765	883	PLASTIC ELECTRAFIL J1300/CF/20/MS/10/TF/15
82766	975	PLASTIC LUBRICOMP SL4040
82767	975	PLASTIC LUBRICOMP SL4610
82768	975	PLASTIC LUBRICOMP T1000
82769	975	PLASTIC LUBRICOMP TF1006
82770	975	PLASTIC LUBRICOMP TFL4036
82771	975	PLASTIC LUBRICOMP TFL4536
82772	975	PLASTIC LUBRICOMP TL4030
82773	883	PLASTIC ELECTRAFIL J1300/CF/30
82774	975	PLASTIC LUBRICOMP TL4410
82775	975	PLASTIC LUBRICOMP V1000
82776	883	PLASTIC ELECTRAFIL J1300/CF/30/TF/15
82777	975	PLASTIC LUBRICOMP VFL4036
82778	883	PLASTIC ELECTRAFIL J1300/CF/40
82779	975	PLASTIC LUBRICOMP VICTREX PEEK D450HF30
82780	883	PLASTIC ELECTRAFIL J1300/CF/50/HM
82781	975	PLASTIC LUBRICOMP VICTREX PEEK D450HT15
82782	883	PLASTIC ELECTRAFIL J1300/CN/15
82783	883	PLASTIC ELECTRAFIL J1300/CN/40
82784	975	PLASTIC LUBRICOMP VICTREX PES 4800G
82785	883	PLASTIC ELECTRAFIL J1400/CF/20
82786	883	PLASTIC ELECTRAFIL J1405/CF/30
82787	976	PLASTIC LUBRICOMP VICTREX PES PDX86174
82788	883	PLASTIC ELECTRAFIL J1500/CF/20
82789	976	PLASTIC LUBRICOMP VL4040
82790	884	PLASTIC ELECTRAFIL J1500/CF/30
82791	976	PLASTIC LUBRICOMP VL4410
82792	884	PLASTIC ELECTRAFIL J1700/CF/10
82793	976	PLASTIC LUBRICOMP VL4530
82794	884	PLASTIC ELECTRAFIL J1700/CF/20
82795	976	PLASTIC LUBRICOMP W1000
82796	884	PLASTIC ELECTRAFIL J1800/CF/30
82797	976	PLASTIC LUBRICOMP WC1006
82798	976	PLASTIC LUBRICOMP WF1006
82799	884	PLASTIC ELECTRAFIL J1850/CF/30
82800	976	PLASTIC LUBRICOMP WFL4036
82801	884	PLASTIC ELECTRAFIL J3/CF/30
82802	976	PLASTIC LUBRICOMP WFL4536
82803	976	PLASTIC LUBRICOMP WL4030
82804	884	PLASTIC ELECTRAFIL J3/CF/40
82805	976	PLASTIC LUBRICOMP WL4410
82806	884	PLASTIC ELECTRAFIL J3/CF/50
82807	884	PLASTIC ELECTRAFIL J30/CF/20
82808	884	PLASTIC ELECTRAFIL J4/CF/30/TF/10
82809	976	PLASTIC LUBRICOMP WL4540
82810	884	PLASTIC ELECTRAFIL J4/CF/40
82811	976	PLASTIC LUBRICOMP X1000
82812	884	PLASTIC ELECTRAFIL J50/CF/10
82813	884	PLASTIC ELECTRAFIL J50/CF/10/TF/15/FR
82814	884	PLASTIC ELECTRAFIL J50/CF/20
82815	885	PLASTIC ELECTRAFIL J50/CF/20/TF/15
82816	885	PLASTIC ELECTRAFIL J50/CF/30
82817	885	PLASTIC ELECTRAFIL J50/CF/40
82818	885	PLASTIC ELECTRAFIL J50/CP/25/FR
82819	976	PLASTIC LUBRICOMP XC1006
82820	885	PLASTIC ELECTRAFIL J60/CF/30
82821	885	PLASTIC ELECTRAFIL J60/CP/40
82822	885	PLASTIC ELECTRAFIL J8/15/CF/15
82823	885	PLASTIC ELECTRAFIL JI/CF/15
82824	977	PLASTIC LUBRICOMP XF1006
82825	885	PLASTIC ELECTRAFIL J80/CF/10/TF/10
82826	885	PLASTIC ELECTRAFIL SMA38/AF/40
82827	977	PLASTIC LUBRICOMP XL4040
82828	904	PLASTIC ETHOFIL G90/20
82829	977	PLASTIC LUBRICOMP Y1000
82830	905	PLASTIC ETHOFIL G90/30
82831	905	PLASTIC ETHOFIL J90/20
82832	977	PLASTIC LUBRICOMP YF1006
82833	905	PLASTIC ETHOFIL J90/30
82834	977	PLASTIC LUBRICOMP YFL4536
82835	906	PLASTIC FIBERFIL G2/10
82836	977	PLASTIC LUBRICOMP YL4030
82837	977	PLASTIC LUBRICOMP YL4410
82838	906	PLASTIC FIBERFIL G2/20
82839	906	PLASTIC FIBERFIL G2/30
82840	977	PLASTIC LUBRICOMP YL4530
82841	906	PLASTIC FIBERFIL G2/40
82842	906	PLASTIC FIBERFIL J1105/30
82843	977	PLASTIC LUBRICOMP Z1000
82844	906	PLASTIC FIBERFIL J1106/20
82845	906	PLASTIC FIBERFIL J1106/30
82846	977	PLASTIC LUBRICOMP ZBL4326
82847	906	PLASTIC FIBERFIL J11106/40
82848	977	PLASTIC LUBRICOMP ZF1006
82849	977	PLASTIC LUBRICOMP ZFL4036
82850	977	PLASTIC LUBRICOMP ZFL4323
82851	906	PLASTIC FIBERFIL J1700/30
82852	906	PLASTIC FIBERFIL J1300/25/MF/40
82853	978	PLASTIC LUBRICOMP ZL4030
82854	978	PLASTIC LUBRICOMP ZML4334
82855	906	PLASTIC FIBERFIL J1700/40
82856	906	PLASTIC FIBERFIL J2/10
82857	906	PLASTIC FIBERFIL J2/20
82858	1,010	PLASTIC NY-KON I
82859	907	PLASTIC FIBERFIL J2/30
82860	1,011	PLASTIC NY-KON P
82861	907	PLASTIC FIBERFIL J2/40
82862	1,011	PLASTIC NY-KON Q
82863	915	PLASTIC FORTIFLEX A6070119
82864	906	PLASTIC FIBERFIL J1700/20
82865	1,011	PLASTIC NY-KON R
82866	1,028	PLASTIC PDX-84369 PBT

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006806 6

MATCD	PAGE	DESIGNATION
82867	913	PLASTIC FORMALDAFIL AC80/TF/10
82868	913	PLASTIC FORMALDAFIL AC80/TF/15
82869	915	PLASTIC FORTIFLEX B35150134
82870	1,028	PLASTIC PDX-82427
82871	913	PLASTIC FORMALDAFIL AC80/TF/20
82872	915	PLASTIC FORTIFLEX B4506R09
82873	913	PLASTIC FORMALDAFIL J80/10
82874	1,028	PLASTIC PDX-82428
82875	914	PLASTIC FORMALDAFIL J80/20
82876	915	PLASTIC FORTIFLEX B5020H
82877	1,028	PLASTIC PDX-83238
82878	1,028	PLASTIC PDX-83392
82879	915	PLASTIC FORTIFLEX B5035H
82880	914	PLASTIC FORMALDAFIL J80/20/TF/15
82881	1,028	PLASTIC PDX-83393
82882	915	PLASTIC FORTIFLEX B5335H
82883	914	PLASTIC FORMALDAFIL J80/30
82884	1,028	PLASTIC PDX-84356
82885	914	PLASTIC FORMALDAFIL J80/30/TF/15
82886	1,028	PLASTIC PDX-84357
82887	915	PLASTIC FORTIFLEX B5335H100
82888	914	PLASTIC FORMALDAFIL J82/10
82889	1,028	PLASTIC PDX-84367 PEI
82890	914	PLASTIC FORMALDAFIL J82/25
82891	1,029	PLASTIC PDX-84440 EVA
82892	915	PLASTIC FORTIFLEX B5335H126
82893	914	PLASTIC FORMALDAFIL J82/40
82894	988	PLASTIC METHAFIL J-98/10
82895	915	PLASTIC FORTIFLEX B5425H
82896	1,117	PLASTIC STAT-KON AC-1003
82897	915	PLASTIC FORTIFLEX B5425H124
82898	988	PLASTIC METHAFIL J-98/20
82899	915	PLASTIC FORTIFLEX B5425H127
82900	1,118	PLASTIC STAT-KON AS-F
82901	988	PLASTIC METHAFIL J-98/30
82902	915	PLASTIC FORTIFLEX B3514F
82903	1,118	PLASTIC STAT-KON AS-FE
82904	988	PLASTIC METHAFIL J-98/40
82905	915	PLASTIC FORTIFLEX F444A
82906	1,118	PLASTIC STAT-KON BLM
82907	1,011	PLASTIC NYAFIL 6
82908	916	PLASTIC FORTIFLEX F469A
82909	1,118	PLASTIC STAT-KON D
82910	1,011	PLASTIC NYAFIL 6/12
82911	1,118	PLASTIC STAT-KON D-FR
82912	916	PLASTIC FORTIFLEX F622
82913	1,118	PLASTIC STAT-KON DC-1003-FR
82914	1,011	PLASTIC NYAFIL G-1/10/CF/30
82915	1,011	PLASTIC NYAFIL G-1/30 AND G-1/30/HS
82916	916	PLASTIC FORTIFLEX G6025119
82917	1,118	PLASTIC STAT-KON DC-1006
82918	916	PLASTIC FORTIFLEX G6080F
82919	1,011	PLASTIC NYAFIL G-1/30/MS/5
82920	916	PLASTIC FORTIFLEX J60100130
82921	1,011	PLASTIC NYAFIL G-1/30/SI/2
82922	916	PLASTIC FORTIFLEX K3411121
82923	1,011	PLASTIC NYAFIL G-1/30/TF/15
82924	916	PLASTIC FORTIFLEX K3655123
82925	1,011	PLASTIC NYAFIL G-1/40
82926	916	PLASTIC FORTIFLEX K3820137
82927	1,118	PLASTIC STAT-KON DCF-1006 15C/15G
82928	1,011	PLASTIC NYAFIL G-1/40/MS/5
82929	916	PLASTIC FORTIFLEX K4411128
82930	1,011	PLASTIC NYAFIL G-1/CF/30
82931	1,118	PLASTIC STAT-KON DCL-4033
82932	1,011	PLASTIC NYAFIL G-3/30
82933	1,118	PLASTIC STAT-KON DF-15
82934	1,012	PLASTIC NYAFIL G-3/40
82935	1,118	PLASTIC STAT-KON DF-FR
82936	916	PLASTIC FORTIFLEX K4415123
82937	1,012	PLASTIC NYAFIL G-4/35
82938	1,118	PLASTIC STAT-KON EC-1003
82939	1,012	PLASTIC NYAFIL G-4/45
82940	916	PLASTIC FORTIFLEX K4424123
82941	1,012	PLASTIC NYAFIL G-8/40
82942	1,118	PLASTIC STAT-KON EC-1006
82943	916	PLASTIC FORTIFLEX K5030135
82944	1,012	PLASTIC NYAFIL J-1/15/MF/25
82945	1,119	PLASTIC STAT-KON FE
82946	916	PLASTIC FORTIFLEX T353500129
82947	1,012	PLASTIC NYAFIL J-1/20/FR
82948	1,119	PLASTIC STAT-KON FP-CC-1004
82949	916	PLASTIC FORTIFLEX T35600
82950	1,119	PLASTIC STAT-KON FP-E
82951	1,012	PLASTIC NYAFIL J-1/30 AND J-1/30/HS
82952	917	PLASTIC FORTIFLEX T491000129
82953	1,012	PLASTIC NYAFIL J-1/30/MS/15
82954	1,119	PLASTIC STAT-KON FP-EC-1004
82955	917	PLASTIC FORTIFLEX T501000
82956	1,119	PLASTIC STAT-KON FP-P
82957	1,012	PLASTIC NYAFIL J-1/30/MS/5
82958	917	PLASTIC FORTIFLEX T50200
82959	1,012	PLASTIC NYAFIL J-1/30/SI/3
82960	1,119	PLASTIC STAT-KON FP-PC-1004
82961	1,012	PLASTIC NYAFIL J-1/30/TF/15
82962	917	PLASTIC FORTIFLEX T502000
82963	1,119	PLASTIC STAT-KON FP-VC-1003
82964	1,012	PLASTIC NYAFIL J-1/33 AND J-1/33/HS
82965	917	PLASTIC FORTIFLEX T503600119
82966	1,119	PLASTIC STAT-KON GC-1003
82967	917	PLASTIC FORTIFLEX T504400119
82968	1,012	PLASTIC NYAFIL J-1/33/TF/13/SI/2
82969	1,119	PLASTIC STAT-KON GC-1006
82970	917	PLASTIC FORTIFLEX T50500
82971	1,012	PLASTIC NYAFIL J-1/40/MU/20
82972	1,119	PLASTIC STAT-KON H
82973	1,013	PLASTIC NYAFIL J-1/43
82974	1,119	PLASTIC STAT-KON IC-1006
82975	1,013	PLASTIC NYAFIL J-1/CF/30
82976	1,119	PLASTIC STAT-KON JC-1003

MSFC-HDBK-527 REV F ■ 9999942 0006807 8 ■

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
82977	917	PLASTIC FORTIFLEX T505500119
82978	1,013	PLASTIC NYAFIL J-1/CF/30/TF/13/SI/2
82979	1,119	PLASTIC STAT-KON JC-1006
82980	1,013	PLASTIC NYAFIL J-1/CP/30
82981	917	PLASTIC FORTIFLEX T601500
82982	1,119	PLASTIC STAT-KON KC-1002
82983	917	PLASTIC FORTIFLEX T603000119
82984	1,013	PLASTIC NYAFIL J-17/20/VO
82985	1,120	PLASTIC STAT-KON KCL-4022
82986	1,013	PLASTIC NYAFIL J-17/20/VO/TF/15
82987	917	PLASTIC FORTIFLEX T604200119
82988	917	PLASTIC FORTIFLEX T60500
82989	1,120	PLASTIC STAT-KON LC-1006
82990	917	PLASTIC FORTIFLEX T60800
82991	1,013	PLASTIC NYAFIL J-17/30/VO
82992	917	PLASTIC FORTIFLEX XF337G
82993	918	PLASTIC FORTIFLEX XF397D
82994	1,013	PLASTIC NYAFIL J-2/30/VO
82995	1,013	PLASTIC NYAFIL J-29/33
82996	1,013	PLASTIC NYAFIL J-29/8/MB/22
82997	1,120	PLASTIC STAT-KON LCL-4033
82998	1,013	PLASTIC NYAFIL J-3/15/MF/25
82999	918	PLASTIC FORTIFLEX XF409
83000	1,013	PLASTIC NYAFIL J-3/30
83001	1,120	PLASTIC STAT-KON M1 HI
83002	918	PLASTIC FORTIFLEX XF448
83003	918	PLASTIC FORTIFLEX XF451
83004	1,120	PLASTIC STAT-KON M2
83005	1,013	PLASTIC NYAFIL J-3/30/VO
83006	918	PLASTIC FORTIFLEX XF455
83007	1,120	PLASTIC STAT-KON ME
83008	1,013	PLASTIC NYAFIL J-3/40
83009	918	PLASTIC FORTIFLEX XF470
83010	1,120	PLASTIC STAT-KON MF-15
83011	918	PLASTIC FORTIFLEX XF480A
83012	1,120	PLASTIC STAT-KON MM3340
83013	918	PLASTIC FORTIFLEX XF528B
83014	1,120	PLASTIC STAT-KON OC-1003
83015	918	PLASTIC FORTIFLEX XF591H
83016	1,014	PLASTIC NYAFIL J-4/30/TF/15
83017	1,014	PLASTIC NYAFIL J-4/30/VO
83018	1,120	PLASTIC STAT-KON OC-1006
83019	918	PLASTIC FORTIFLEX XF600
83020	1,014	PLASTIC NYAFIL J-4/35
83021	1,120	PLASTIC STAT-KON OCL-4036
83022	1,014	PLASTIC NYAFIL J-4/45
83023	1,014	PLASTIC NYAFIL J-4/CF/40
83024	918	PLASTIC FORTIFLEX XF621
83025	1,014	PLASTIC NYAFIL J-6/25
83026	918	PLASTIC FORTILENE 1001
83027	1,014	PLASTIC NYAFIL J-6/50
83028	1,120	PLASTIC STAT-KON PC-1002
83029	1,120	PLASTIC STAT-KON PC-1006
83030	918	PLASTIC FORTILENE 10 X 03
83031	1,014	PLASTIC NYAFIL J-7/13
83032	1,014	PLASTIC NYAFIL J-7/33
83033	918	PLASTIC FORTILENE 1401
83034	1,120	PLASTIC STAT-KON PDX-84368 PC
83035	1,014	PLASTIC NYAFIL J-7/43
83036	919	PLASTIC FORTILENE 1420
83037	1,121	PLASTIC STAT-KON QC-1002
83038	1,014	PLASTIC NYAFIL J-70/30
83039	1,121	PLASTIC STAT-KON QC-1006
83040	919	PLASTIC FORTILENE 1602
83041	1,121	PLASTIC STAT-KON R
83042	1,121	PLASTIC STAT-KON RC-1002
83043	919	PLASTIC FORTILENE 1602A
83044	1,121	PLASTIC STAT-KON RC-1004
83045	919	PLASTIC FORTILENE 1604
83046	1,121	PLASTIC STAT-KON RC-1004-FR
83047	1,014	PLASTIC NYAFIL J-71/20
83048	1,121	PLASTIC STAT-KON RC-1006
83049	1,121	PLASTIC STAT-KON RC-1006-HI
83050	1,014	PLASTIC NYAFIL J-8/13
83051	1,121	PLASTIC STAT-KON RCF-1006
83052	919	PLASTIC FORTILENE 1802
83053	1,014	PLASTIC NYAFIL J-8/30
83054	1,121	PLASTIC STAT-KON RCL-4036
83055	1,015	PLASTIC NYAFIL J-8/33
83056	1,121	PLASTIC STAT-KON RCL-4042
83057	1,015	PLASTIC NYAFIL J-8/43
83058	1,015	PLASTIC NYAFIL MG-1/40
83059	1,121	PLASTIC STAT-KON RCL-4536
83060	1,015	PLASTIC NYAFIL NY-1/EC
83061	919	PLASTIC FORTILENE 1803
83062	919	PLASTIC FORTILENE 1804
83063	1,121	PLASTIC STAT-KON RF-15
83064	1,015	PLASTIC NYAFIL NY-1/MS/5
83065	1,015	PLASTIC NYAFIL NY-1/SI/5
83066	1,121	PLASTIC STAT-KON T
83067	919	PLASTIC FORTILENE 1805
83068	1,122	PLASTIC STAT-KON VC-1003
83069	919	PLASTIC FORTILENE 1902
83070	1,122	PLASTIC STAT-KON WC-1002
83071	919	PLASTIC FORTILENE 1903
83072	1,015	PLASTIC NYAFIL NY-1/TC/30
83073	1,122	PLASTIC STAT-KON WC-1006
83074	1,015	PLASTIC NYAFIL NY-1/TF/15
83075	919	PLASTIC FORTILENE 21 X 04
83076	1,015	PLASTIC NYAFIL NY-16/MF/40
83077	1,122	PLASTIC STAT-KON ZC-1003
83078	919	PLASTIC FORTILENE 2251
83079	1,015	PLASTIC NYAFIL NY-17/MF/40
83080	1,118	PLASTIC STAT-KON AC-1006
83081	1,016	PLASTIC NYAFIL NY3/20/75
83082	919	PLASTIC FORTILENE 22 X 02
83083	919	PLASTIC FORTILENE 3151
83084	1,164	PLASTIC THERMOCOMP AF-1004
83085	920	PLASTIC FORTILENE 3251
83086	920	PLASTIC FORTILENE 3606

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006808 T

MATCD	PAGE	DESIGNATION
83087	920	PLASTIC FORTILENE 3651
83088	920	PLASTIC FORTILENE 3807
83089	920	PLASTIC FORTILENE 3907
83090	920	PLASTIC FORTILENE 39 X 09
83091	920	PLASTIC FORTILENE 40 X 05
83092	920	PLASTIC FORTILENE 4104
83093	920	PLASTIC FORTILENE 4109
83094	920	PLASTIC FORTILENE 4110
83095	920	PLASTIC FORTILENE 4141
83096	920	PLASTIC FORTILENE 41 X 03
83097	920	PLASTIC FORTILENE 41 X 11
83098	920	PLASTIC FORTILENE 4207
83099	921	PLASTIC FORTILENE 4208
83100	921	PLASTIC FORTILENE 4306
83101	921	PLASTIC FORTILENE 45 X 02
83102	921	PLASTIC FORTILENE 5402
83103	921	PLASTIC FORTILENE 9000
83104	921	PLASTIC FORTILENE 9005
83105	921	PLASTIC FORTILENE 90 X 02
83106	921	PLASTIC FORTILENE 9101
83107	921	PLASTIC FORTILENE 9200
83108	921	PLASTIC FORTILENE 9205
83109	921	PLASTIC FORTILENE 9226
83110	921	PLASTIC FORTILENE 9600
83111	921	PLASTIC FORTILENE 9605
83112	921	PLASTIC FORTILENE 9625
83113	1,113	PLASTIC RTV SWS04478
83114	1,113	PLASTIC RTV SWS843
83115	231	ADHESIVE RTV T200
83116	231	ADHESIVE RTV T56
83117	1,280	RUBBER DUOTHANE N1545A
83118	1,280	RUBBER DUOTHANE N1545B
83119	1,280	RUBBER DUOTHANE N1545C
83120	1,280	RUBBER DUOTHANE N1545D
83121	1,280	RUBBER DUOTHANE N4209
83122	1,280	RUBBER DUOTHANE N6766
83123	1,280	RUBBER DUOTHANE S300
83124	1,280	RUBBER DUOTHANE S401
83125	1,280	RUBBER DUOTHANE S502
83126	1,280	RUBBER DUOTHANE S504
83127	1,280	RUBBER DUOTHANE S600
83128	1,280	RUBBER DUOTHANE S601
83129	1,281	RUBBER DUOTHANE S602
83130	1,281	RUBBER DUOTHANE S603 (REDCOTE)
83131	1,281	RUBBER DUOTHANE S700
83132	1,281	RUBBER DUOTHANE S701
83133	1,281	RUBBER DUOTHANE S702
83134	1,281	RUBBER DUOTHANE S800
83135	1,281	RUBBER DUOTHANE S802
83136	1,281	RUBBER DUOTHANE S803
83137	1,281	RUBBER DUOTHANE S900
83138	1,281	RUBBER DUOTHANE S901
83139	1,299	RUBBER MONOTHANE A10
83140	1,299	RUBBER MONOTHANE A100
83141	1,299	RUBBER MONOTHANE A20
83142	1,299	RUBBER MONOTHANE A30
83143	1,299	RUBBER MONOTHANE A40
83144	1,300	RUBBER MONOTHANE A50
83145	1,300	RUBBER MONOTHANE A60
83146	1,300	RUBBER MONOTHANE A70
83147	1,300	RUBBER MONOTHANE A80
83148	1,300	RUBBER MONOTHANE A90
83149	1,300	RUBBER MONOTHANE A40HR
83150	1,300	RUBBER MONOTHANE A45SR
83151	256	ADHESIVE TECKBOND 72-00118
83152	256	ADHESIVE TECKBOND 72-00119
83153	257	ADHESIVE TECKBOND 72-00125
83154	1,279	RUBBER CONSIL C875 CONDUCTIVE FLUOROSILICONE
83155	1,280	RUBBER CONSIL R854 CONDUCTIVE FLUOROSILICONE
83156	1,279	RUBBER CONSIL R HT
83157	1,384	RUBBER VULCON CL 1 GR 40 T2
83158	1,384	RUBBER VULCON SILICONE
83159	1,384	RUBBER VULCON CL 2 GR 40
83160	822	PLASTIC APEX 1001
83161	822	PLASTIC APEX 1002
83162	822	PLASTIC APEX 1003
83163	822	PLASTIC APEX 1004
83164	822	PLASTIC APEX 1007
83165	822	PLASTIC APEX 1008
83166	822	PLASTIC APEX 1009
83167	822	PLASTIC APEX 1011
83168	822	PLASTIC APEX 1013
83169	822	PLASTIC APEX 1015
83170	822	PLASTIC APEX 1216
83171	822	PLASTIC APEX 1217
83172	823	PLASTIC APEX 1221
83173	823	PLASTIC APEX 1369
83174	823	PLASTIC APEX 1464
83175	823	PLASTIC APEX 1521
83176	823	PLASTIC APEX 1522
83177	823	PLASTIC APEX 1523
83178	823	PLASTIC APEX 1524
83179	823	PLASTIC APEX 1525
83180	823	PLASTIC APEX 1526
83181	823	PLASTIC APEX 1527
83182	823	PLASTIC APEX 1560
83183	823	PLASTIC APEX 1561
83184	823	PLASTIC APEX 1562
83185	823	PLASTIC APEX 1563
83186	824	PLASTIC APEX 1564
83187	824	PLASTIC APEX 1565
83188	824	PLASTIC APEX 1566
83189	824	PLASTIC APEX 1581
83190	824	PLASTIC APEX 1582
83191	824	PLASTIC APEX 1583
83192	824	PLASTIC APEX 1584
83193	824	PLASTIC APEX 1585
83194	824	PLASTIC APEX 1586
83195	824	PLASTIC APEX 1587
83196	824	PLASTIC APEX 1589

MSFC-HDBK-527 REV F 9999942 0006809 1

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
83197	824	PLASTIC APEX 1590
83198	824	PLASTIC APEX 1835
83199	824	PLASTIC APEX 1850
83200	825	PLASTIC APEX 1877
83201	825	PLASTIC APEX 370
83202	825	PLASTIC APEX 4101
83203	825	PLASTIC APEX 4103
83204	825	PLASTIC APEX 4109
83205	825	PLASTIC APEX 4217
83206	825	PLASTIC APEX 776
83207	1,366	RUBBER TELCAR 101
83208	1,366	RUBBER TELCAR 102
83209	1,366	RUBBER TELCAR 150
83210	1,366	RUBBER TELCAR 301
83211	1,366	RUBBER TELCAR 302
83212	1,366	RUBBER TELCAR 310
83213	1,366	RUBBER TELCAR 312
83214	1,366	RUBBER TELCAR 332
83215	1,366	RUBBER TELCAR 340
83216	1,366	RUBBER TELCAR 340S
83217	1,366	RUBBER TELCAR 340E
83218	1,366	RUBBER TELCAR 355
83219	1,160	PLASTIC TETRAFLUOR TF619
83220	1,161	PLASTIC TETRAFLUOR TFC021
83221	1,161	PLASTIC TETRAFLUOR TFC025
83222	1,161	PLASTIC TETRAFLUOR TFC030
83223	1,161	PLASTIC TETRAFLUOR TFC031
83224	1,161	PLASTIC TETRAFLUOR TFC033
83225	1,161	PLASTIC TETRAFLUOR TFC045
83226	1,161	PLASTIC TETRAFLUOR TFC082
83227	1,161	PLASTIC TETRAFLUOR TFC086
83228	1,161	PLASTIC TETRAFLUOR TFC108
83229	1,161	PLASTIC TETRAFLUOR TFC608
83230	1,161	PLASTIC TETRAFLUOR TFC616
83231	1,161	PLASTIC TETRAFLUOR TFC617
83232	1,161	PLASTIC TETRAFLUOR TFC618
83233	1,161	PLASTIC TETRALON
83234	1,162	PLASTIC TETRALON 510
83235	1,162	PLASTIC TETRALON 710
83236	1,162	PLASTIC TETRALON TFC031
83237	1,162	PLASTIC TETRALON TFC033
83238	1,015	PLASTIC NYAFIL NY-3/EC
83239	1,015	PLASTIC NYAFIL NY-3/TC/40
83240	1,015	PLASTIC NYAFIL NY-7
83241	1,015	PLASTIC NYAFIL NY-8
83242	1,016	PLASTIC NYAFIL NY-8/MF/36
83243	1,016	PLASTIC NYAFIL TYPE 6/10 NYLON UNREINFORCED
83244	1,016	PLASTIC NYAFIL UNREINFORCED 612
83245	1,016	PLASTIC NYAFIL UNREINFORCED SUPER TOUGH TYPE 12
83246	1,016	PLASTIC NYAFIL UNREINFORCED TYPE 12
83247	1,016	PLASTIC NYAFIL UNREINFORCED TYPE 6
83248	1,016	PLASTIC NYAFIL UNREINFORCED TYPE 66
83249	1,016	PLASTIC NYAFIL XYLON FR
83250	1,016	PLASTIC NYAFIL XYLON/VO
83251	1,016	PLASTIC NYAFIL VO NY-7/VO
83252	1,043	PLASTIC PLASTALLOY J-1505/10
83253	1,043	PLASTIC PLASTALLOY J-1505/30
83254	1,043	PLASTIC PLASTALLOY J-1505/40
83255	1,054	PLASTIC POLYCARBAFIL F-50/20/FR
83256	1,054	PLASTIC POLYCARBAFIL G-50/20/FR
83257	1,054	PLASTIC POLYCARBAFIL G-50/30
83258	1,055	PLASTIC POLYCARBAFIL J-50/20/FR
83259	1,055	PLASTIC POLYCARBAFIL J-5/30/FR
83260	1,055	PLASTIC POLYCARBAFIL J-50/40
83261	1,164	PLASTIC THERMOCOMP AF-1006
83262	1,055	PLASTIC POLYCARBAFIL J-50/M/5/CE/10
83263	1,055	PLASTIC POLYCARBAFIL J-54/10
83264	1,164	PLASTIC THERMOCOMP AF-1008
83265	1,164	PLASTIC THERMOCOMP BF-1004
83266	1,055	PLASTIC POLYCARBAFIL/FOAM F-50/10
83267	1,164	PLASTIC THERMOCOMP BF-1006
83268	1,165	PLASTIC THERMOCOMP BF-1006FR
83269	1,055	PLASTIC POLYCARBAFIL/FOAM F-50/20
83270	1,165	PLASTIC THERMOCOMP BF-1007
83271	1,165	PLASTIC THERMOCOMP BF-1008
83272	1,055	PLASTIC POLYCARBAFIL/FOAM F-50/20 LONG GLASS
83273	1,165	PLASTIC THERMOCOMP CF-1004
83274	1,055	PLASTIC POLYCARBAFIL/FOAM F-50/30
83275	1,165	PLASTIC THERMOCOMP CF-1006
83276	1,055	PLASTIC POLYCARBAFIL/FOAM F-50/40
83277	1,165	PLASTIC THERMOCOMP DC-1003FR
83278	1,087	PLASTIC PROFIL G-60/20
83279	1,087	PLASTIC PROFIL G-60/30
83280	1,165	PLASTIC THERMOCOMP DC-1006
83281	1,087	PLASTIC PROFIL J-60/10/E3
83282	1,165	PLASTIC THERMOCOMP DC-1006PC
83283	1,088	PLASTIC PROFIL J-60/10/E4
83284	1,165	PLASTIC THERMOCOMP DF-1004
83285	1,165	PLASTIC THERMOCOMP DF-1006
83286	1,165	PLASTIC THERMOCOMP DF-1008
83287	1,088	PLASTIC PROFIL J-60/20
83288	1,165	PLASTIC THERMOCOMP DFA-113
83289	1,088	PLASTIC PROFIL J-60/20/E
83290	1,165	PLASTIC THERMOCOMP DFL-4036
83291	1,088	PLASTIC PROFIL J-60/20/E3
83292	1,165	PLASTIC THERMOCOMP DL-4020FR
83293	1,088	PLASTIC PROFIL J-60/20/E4
83294	1,166	PLASTIC THERMOCOMP DL-4030
83295	1,088	PLASTIC PROFIL J-60/30
83296	1,088	PLASTIC PROFIL J-60/30/E
83297	1,166	PLASTIC THERMOCOMP EC-1006
83298	1,088	PLASTIC PROFIL J-60/30/ER
83299	1,088	PLASTIC PROFIL J-60/40
83300	1,166	PLASTIC THERMOCOMP EC-1008
83301	1,088	PLASTIC PROFIL J-60/40/E
83302	1,166	PLASTIC THERMOCOMP EF-1004
83303	1,088	PLASTIC PROFIL J-60/40/E3
83304	1,166	PLASTIC THERMOCOMP EF-1006
83305	1,166	PLASTIC THERMOCOMP EF-1008
83306	1,088	PLASTIC PROFIL J-60/40/ER

MSFC-HDBK-527 REV F 9999942 0006810 8

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
83307	1,088	PLASTIC PROFIL J-61/10/NAT
83308	1,166	PLASTIC THERMOCOMP EFL-4036
83309	1,089	PLASTIC PROFIL J-61/20/NAT
83310	1,089	PLASTIC PROFIL J-61/30/NAT
83311	1,166	PLASTIC THERMOCOMP FC-102CF
83312	1,166	PLASTIC THERMOCOMP FF-1004
83313	1,166	PLASTIC THERMOCOMP FF-1006
83314	1,166	PLASTIC THERMOCOMP FF-1008
83315	1,166	PLASTIC THERMOCOMP FP-EC-1004
83316	1,166	PLASTIC THERMOCOMP FP-PC-1003
83317	1,166	PLASTIC THERMOCOMP FP-VC-1003
83318	1,167	PLASTIC THERMOCOMP FULTON 441
83319	1,167	PLASTIC THERMOCOMP FULTON 441D
83320	1,089	PLASTIC PROFIL J-61/40/NAT
83321	1,089	PLASTIC PROFIL J-62/10/E4
83322	1,089	PLASTIC PROFIL J-62/20/E4
83323	1,089	PLASTIC PROFIL J-62/30/E4
83324	1,089	PLASTIC PROFIL J-62/40/E4
83325	1,089	PLASTIC PROFIL PF-6000
83326	1,089	PLASTIC PROFIL PF-6000/EC
83327	1,089	PLASTIC PROFIL PF-6001
83328	1,089	PLASTIC PROFIL PF-6010
83329	1,089	PLASTIC PROFIL PF-6012
83330	1,089	PLASTIC PROFIL PF-6013
83331	1,089	PLASTIC PROFIL PF6020
83332	1,167	PLASTIC THERMOCOMP GC-1006
83333	1,090	PLASTIC PROFIL PF6022
83334	1,090	PLASTIC PROFIL PF6023
83335	1,167	PLASTIC THERMOCOMP GF-1004
83336	1,167	PLASTIC THERMOCOMP GF-1006
83337	1,090	PLASTIC PROFIL PF6024
83338	1,090	PLASTIC PROFIL PP-60/CC/20
83339	1,090	PLASTIC PROFIL PP-60/CC/40
83340	1,090	PLASTIC PROFIL PP-60 FR
83341	1,167	PLASTIC THERMOCOMP GF-1006FR
83342	1,090	PLASTIC PROFIL PP-60/TC/20
83343	1,090	PLASTIC PROFIL PP-60/TC/40
83344	1,167	PLASTIC THERMOCOMP GF-1008
83345	1,090	PLASTIC PROFIL PP-61/CC/20
83346	1,167	PLASTIC THERMOCOMP HF-1006
83347	1,090	PLASTIC PROFIL PP-61/CC/40
83348	1,090	PLASTIC PROFIL PP-61/TC/20
83349	1,090	PLASTIC PROFIL PP-61/TC/40
83350	1,090	PLASTIC PROFIL PP-62/TC/20
83351	1,167	PLASTIC THERMOCOMP IC-1006
83352	1,091	PLASTIC PROFIL PP-62/TC/40
83353	1,090	PLASTIC PROFIL PP-62/MI/40
83354	1,162	PLASTIC TEXALON 1106A
83355	1,162	PLASTIC TEXALON 1108A
83356	1,162	PLASTIC TEXALON 1110 AL PL2 HS BK18
83357	1,162	PLASTIC TEXALON 1200A
83358	1,162	PLASTIC TEXALON 1200A FR
83359	1,162	PLASTIC TEXALON 1200A HS
83360	1,162	PLASTIC TEXALON 1200A ZIP
83361	1,162	PLASTIC TEXALON 1200A ZIP 10
83362	1,162	PLASTIC TEXALON 1200A ZIP 10 BX11
83363	1,162	PLASTIC TEXALON 1203D ZIP 10
83364	1,163	PLASTIC TEXALON 1308A
83365	1,163	PLASTIC TEXALON 1310
83366	1,163	PLASTIC TEXALON 600A
83367	1,163	PLASTIC TEXALON 600A HS
83368	1,163	PLASTIC TEXALON 600A HV HS
83369	1,163	PLASTIC TEXALON 600A PL2
83370	1,163	PLASTIC TEXALON 600A ZIP
83371	1,163	PLASTIC TEXALON 600A ZIP 10
83372	1,163	PLASTIC TEXALON 623 HS BK13
83373	1,163	PLASTIC TEXALON 680A
83374	1,163	PLASTIC TEXALON GF 1200 A33
83375	1,163	PLASTIC TEXALON GF 1308 A13
83376	1,163	PLASTIC TEXALON GF 1310-13
83377	1,163	PLASTIC TEXALON GF 600 A33
83378	1,164	PLASTIC TEXALON GMF 600-40
83379	1,164	PLASTIC TEXALON MF 1200A-40
83380	1,164	PLASTIC TEXALON MF 1200A1-40
83381	1,088	PLASTIC PROFIL J-60/30/FR
83382	1,164	PLASTIC TEXALON MF 600-40
83383	1,164	PLASTIC TEXALON XP1296
83384	1,164	PLASTIC TEXALON XP1317
83385	1,164	PLASTIC TEXALON XP1319 HS
83386	1,176	PLASTIC THERMOFIL A 20FG0100
83387	1,176	PLASTIC THERMOFIL A 35FG0100
83388	1,176	PLASTIC THERMOFIL A1 20FG0570
83389	1,176	PLASTIC THERMOFIL A1 20FG0700
83390	1,176	PLASTIC THERMOFIL B 20FG0100
83391	1,176	PLASTIC THERMOFIL B 35FB0100
83392	1,176	PLASTIC THERMOFIL B 35FG0100
83393	1,176	PLASTIC THERMOFIL D 10FG0100
83394	1,176	PLASTIC THERMOFIL D 20FG0100
83395	1,176	PLASTIC THERMOFIL D 20FG0500
83396	1,176	PLASTIC THERMOFIL D 30FG0100
83397	1,176	PLASTIC THERMOFIL D 9900-6500
83398	1,176	PLASTIC THERMOFIL E 15FG0100
83399	1,177	PLASTIC THERMOFIL E 15FG0590
83400	1,177	PLASTIC THERMOFIL E 30FG0100
83401	1,177	PLASTIC THERMOFIL E 30FG0590
83402	1,177	PLASTIC THERMOFIL E 30NF0100
83403	1,177	PLASTIC THERMOFIL E 40FG0100
83404	1,177	PLASTIC THERMOFIL E 40MI0100
83405	1,177	PLASTIC THERMOFIL E 45FM0319
83406	1,177	PLASTIC THERMOFIL E 45FM0393
83407	1,177	PLASTIC THERMOFIL E 9900-0590
83408	1,177	PLASTIC THERMOFIL E1 10FG0100
83409	1,177	PLASTIC THERMOFIL E1 30FG0100
83410	1,177	PLASTIC THERMOFIL E1 30FG0584
83411	1,177	PLASTIC THERMOFIL E2 30FG0100/E2 30FG0578
83412	1,178	PLASTIC THERMOFIL E2 30FG7100
83413	1,178	PLASTIC THERMOFIL E2 30NF0100
83414	1,178	PLASTIC THERMOFIL E2 45FM0393
83415	1,178	PLASTIC THERMOFIL E2 55FG0100
83416	1,177	PLASTIC THERMOFIL E 30FG0287

MSFC-HDBK-527 REV F 9999942 0006811 T

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
83417	1,178	PLASTIC THERMOFIL F 10FG0100
83418	1,178	PLASTIC THERMOFIL F 30FG0100
83419	1,178	PLASTIC THERMOFIL G 20FG0214
83420	1,178	PLASTIC THERMOFIL G 20NF0100
83421	1,178	PLASTIC THERMOFIL G 30FG0100
83422	1,178	PLASTIC THERMOFIL G 9900-0215
83423	1,178	PLASTIC THERMOFIL G 900-0257
83424	1,178	PLASTIC THERMOFIL K 20FG0100
83425	1,178	PLASTIC THERMOFIL K 30FG0100
83426	1,178	PLASTIC THERMOFIL K 30FG0214
83427	1,179	PLASTIC THERMOFIL K 30NF0100
83428	1,179	PLASTIC THERMOFIL K2 30FG0100
83429	1,179	PLASTIC THERMOFIL K2 30NF0100
83430	1,179	PLASTIC THERMOFIL L 20FG0100
83431	1,179	PLASTIC THERMOFIL L 30FG0100
83432	1,179	PLASTIC THERMOFIL L1 30FG0580
83433	1,179	PLASTIC THERMOFIL N 15FG0100
83434	1,179	PLASTIC THERMOFIL N 15FG0500
83435	1,179	PLASTIC THERMOFIL N 30FG0100
83436	1,179	PLASTIC THERMOFIL N 30FG0214
83437	1,179	PLASTIC THERMOFIL N 30FG0500
83438	1,179	PLASTIC THERMOFIL N 30NF0100
83439	1,179	PLASTIC THERMOFIL N 40BG0100
83440	1,179	PLASTIC THERMOFIL N 40FM0100
83441	1,180	PLASTIC THERMOFIL N 40MF0100
83442	1,180	PLASTIC THERMOFIL N 9900-0500
83443	1,180	PLASTIC THERMOFIL N11 30FG0100
83444	1,180	PLASTIC THERMOFIL N11 30NF0100
83445	1,180	PLASTIC THERMOFIL N11 40MF0350
83446	1,180	PLASTIC THERMOFIL N12 30FG0100
83447	1,180	PLASTIC THERMOFIL N12 30FG0282
83448	1,180	PLASTIC THERMOFIL N12 30FG0500
83449	1,180	PLASTIC THERMOFIL N12 30NF0100
83450	1,180	PLASTIC THERMOFIL N3 13FG0100
83451	1,180	PLASTIC THERMOFIL N3 13FG0700
83452	1,180	PLASTIC THERMOFIL N3 15FG0560
83453	1,180	PLASTIC THERMOFIL N3 20NF0100
83454	1,180	PLASTIC THERMOFIL N3 30FG0214
83455	1,181	PLASTIC THERMOFIL N3 30FG0231
83456	1,181	PLASTIC THERMOFIL N3 30FR0282
83457	1,181	PLASTIC THERMOFIL N3 30FG0560
83458	1,181	PLASTIC THERMOFIL N3 30NF0214
83459	1,181	PLASTIC THERMOFIL N3 33FG0100
83460	1,181	PLASTIC THERMOFIL N3 33FG0700
83461	1,181	PLASTIC THERMOFIL N3 35FM0310
83462	1,181	PLASTIC THERMOFIL N3 40MF0350
83463	1,181	PLASTIC THERMOFIL N3 40MF8300
83464	1,181	PLASTIC THERMOFIL N3 40NF0100
83465	1,181	PLASTIC THERMOFIL N3 43FG0100
83466	1,181	PLASTIC THERMOFIL N3 9900-0200
83467	1,181	PLASTIC THERMOFIL N3 9900-0214
83468	1,181	PLASTIC THERMOFIL N3 9900-0231
83469	1,182	PLASTIC THERMOFIL N3 9900-0279
83470	1,182	PLASTIC THERMOFIL N3 9900-0560
83471	1,182	PLASTIC THERMOFIL N5 15FG0100
83472	1,182	PLASTIC THERMOFIL N5 30FG0100
83473	1,182	PLASTIC THERMOFIL N6 30FG0100
83474	1,182	PLASTIC THERMOFIL N6 30FG0214
83475	1,182	PLASTIC THERMOFIL N6 30FG0282
83476	1,182	PLASTIC THERMOFIL N6 30FG0500
83477	1,182	PLASTIC THERMOFIL N6 30NF0100
83478	1,182	PLASTIC THERMOFIL N6 9900-0500
83479	1,182	PLASTIC THERMOFIL N7 13FG0100
83480	1,182	PLASTIC THERMOFIL N7 20FG0500
83481	1,182	PLASTIC THERMOFIL N7 20NF0100
83482	1,182	PLASTIC THERMOFIL N7 30FG0100
83483	1,183	PLASTIC THERMOFIL N7 35MF7365
83484	1,183	PLASTIC THERMOFIL N7 9900-0500
83485	1,183	PLASTIC THERMOFIL N8 30FG0100
83486	1,183	PLASTIC THERMOFIL N9 30FG0100
83487	1,183	PLASTIC THERMOFIL P 10FG0100
83488	1,183	PLASTIC THERMOFIL P 20FG0100
83489	1,183	PLASTIC THERMOFIL P 20FG0500
83490	1,183	PLASTIC THERMOFIL P 20FG0720
83491	1,183	PLASTIC THERMOFIL P 20MF0500
83492	1,183	PLASTIC THERMOFIL P 20MI0100
83493	1,183	PLASTIC THERMOFIL P 30FG0100
83494	1,183	PLASTIC THERMOFIL P 40CC0100
83495	1,183	PLASTIC THERMOFIL P 40CC0720
83496	1,183	PLASTIC THERMOFIL P 40MI0100
83497	1,184	PLASTIC THERMOFIL P 40MI0720
83498	1,184	PLASTIC THERMOFIL P 40TC0100
83499	1,184	PLASTIC THERMOFIL P 9900-0500
83500	1,184	PLASTIC THERMOFIL P 9900-0570
83501	1,184	PLASTIC THERMOFIL P1 10FG0100
83502	1,184	PLASTIC THERMOFIL P1 20FG0100
83503	1,184	PLASTIC THERMOFIL P1 20FG0720
83504	1,184	PLASTIC THERMOFIL P1 30FG0100
83505	1,184	PLASTIC THERMOFIL P6 10FG0100
83506	1,184	PLASTIC THERMOFIL P6 20FG0100
83507	1,184	PLASTIC THERMOFIL P6 20FG0500
83508	1,184	PLASTIC THERMOFIL P6 20FG0570
83509	1,184	PLASTIC THERMOFIL P6 30FG0100
83510	1,184	PLASTIC THERMOFIL P6 30FG0720
83511	1,185	PLASTIC THERMOFIL R 10FG0100
83512	1,185	PLASTIC THERMOFIL R 10FG0568
83513	1,185	PLASTIC THERMOFIL R 20NF0214
83514	1,185	PLASTIC THERMOFIL R 30FG0100
83515	1,185	PLASTIC THERMOFIL R 30FG0214
83516	1,185	PLASTIC THERMOFIL R 30FG0568
83517	1,185	PLASTIC THERMOFIL R 40NF0100
83518	1,185	PLASTIC THERMOFIL R 9900-0200
83519	1,185	PLASTIC THERMOFIL R 9900-0214
83520	1,185	PLASTIC THERMOFIL R2 10FG0100
83521	1,185	PLASTIC THERMOFIL R2 30FG0100
83522	1,185	PLASTIC THERMOFIL S 20FG0100
83523	1,185	PLASTIC THERMOFIL S 30FG0214
83524	1,185	PLASTIC THERMOFIL S 30MF0360
83525	1,091	PLASTIC PROFIL/FOAM F-60/20
83526	1,129	PLASTIC STYRAFIL G-30/20

MSFC-HDBK-527 REV F 9999942 0006812 1

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
83527	1,129	PLASTIC STYRAFIL G-30/30
83528	1,129	PLASTIC STYRAFIL G-35/35
83529	1,129	PLASTIC STYRAFIL J-30/20
83530	1,129	PLASTIC STYRAFIL J-30/30
83531	1,129	PLASTIC STYRAFIL J-39/10
83532	1,167	PLASTIC THERMOCOMP IF-100-10
83533	1,130	PLASTIC STYRAFIL J-39/10/E
83534	1,167	PLASTIC THERMOCOMP IF-100-12
83535	1,130	PLASTIC STYRAFIL J-39/20
83536	1,130	PLASTIC STYRAFIL J-39/20/D
83537	1,167	PLASTIC THERMOCOMP IF-1002
83538	1,130	PLASTIC STYRAFIL J-39/20/E
83539	1,167	PLASTIC THERMOCOMP IF-1004
83540	1,130	PLASTIC STYRAFIL J-39/30
83541	1,130	PLASTIC STYRAFIL J-39/30/E
83542	1,168	PLASTIC THERMOCOMP IF-1006
83543	1,168	PLASTIC THERMOCOMP IF-1008
83544	1,130	PLASTIC STYRAFIL J-39/40
83545	1,168	PLASTIC THERMOCOMP JC-1006
83546	1,168	PLASTIC THERMOCOMP JCL-4036
83547	1,130	PLASTIC STYRAFIL J-39/40/E
83548	1,168	PLASTIC THERMOCOMP JF-1006
83549	1,131	PLASTIC SULFIL G-1500/10
83550	1,168	PLASTIC THERMOCOMP KB-1008
83551	1,131	PLASTIC SULFIL G-1500/20
83552	1,168	PLASTIC THERMOCOMP KC-1004
83553	1,131	PLASTIC SULFIL J-1100/20
83554	1,168	PLASTIC THERMOCOMP KF-1006
83555	1,168	PLASTIC THERMOCOMP KFX-1002
83556	1,168	PLASTIC THERMOCOMP KFX-1006
83557	1,168	PLASTIC THERMOCOMP KFX-1008MG
83558	1,131	PLASTIC SULFIL J-1100/30
83559	1,168	PLASTIC THERMOCOMP MF-1002
83560	1,168	PLASTIC THERMOCOMP MF-1002HI
83561	1,131	PLASTIC SULFIL J-1100/40
83562	1,168	PLASTIC THERMOCOMP MF-1004
83563	1,131	PLASTIC SULFIL J-1105/30
83564	1,169	PLASTIC THERMOCOMP MF-1004HI
83565	1,131	PLASTIC SULFIL J-1300/10
83566	1,169	PLASTIC THERMOCOMP MF-1004FR
83567	1,131	PLASTIC SULFIL J-1300/20
83568	1,169	PLASTIC THERMOCOMP MF-1004HS
83569	1,131	PLASTIC SULFIL J-1300/30
83570	1,169	PLASTIC THERMOCOMP MF-1006
83571	1,132	PLASTIC SULFIL J-1300/30/TF/15
83572	1,132	PLASTIC SULFIL J-1300/40
83573	1,169	PLASTIC THERMOCOMP MF-1006HS
83574	1,132	PLASTIC SULFIL J-1500/10
83575	1,169	PLASTIC THERMOCOMP MF-1006HI
83576	1,132	PLASTIC SULFIL J-1500/20
83577	1,169	PLASTIC THERMOCOMP MF-1008
83578	1,169	PLASTIC THERMOCOMP MF-1008HI
83579	1,132	PLASTIC SULFIL J-1500/20/TF/15
83580	1,132	PLASTIC SULFIL J-1500/30
83581	1,169	PLASTIC THERMOCOMP MF-1008HS
83582	1,132	PLASTIC SULFIL J-1500/40
83583	1,169	PLASTIC THERMOCOMP MFX-1004HS
83584	1,132	PLASTIC SULFIL J-1505/20
83585	1,160	PLASTIC TETRAFIL J-1800/30
83586	1,169	PLASTIC THERMOCOMP MFX-1006HS
83587	1,160	PLASTIC TETRAFIL J-1800/30/VO
83588	1,169	PLASTIC THERMOCOMP MFX-1008HS
83589	1,160	PLASTIC TETRAFIL J-1800/45
83590	1,160	PLASTIC TETRAFIL J-1800/55
83591	1,169	PLASTIC THERMOCOMP MOS2 LUBED NYLON
83593	1,160	PLASTIC TETRAFIL J-1850/15
83594	1,169	PLASTIC THERMOCOMP NF1004
83595	1,160	PLASTIC TETRAFIL J-1850/30/VO
83596	1,160	PLASTIC TETRAFIL J1875/30/VO
83597	1,236	PLASTIC XYLON/VO NYLON UNREINFORCED
83598	1,170	PLASTIC THERMOCOMP NF1006
83599	1,170	PLASTIC THERMOCOMP NF1008
83600	1,170	PLASTIC THERMOCOMP OC-1006
83601	1,170	PLASTIC THERMOCOMP OCL-4036
83602	1,170	PLASTIC THERMOCOMP OF-1006
83603	1,170	PLASTIC THERMOCOMP OF-1008
83604	1,170	PLASTIC THERMOCOMP OFL-4036
83605	1,170	PLASTIC THERMOCOMP PC-1006
83606	1,170	PLASTIC THERMOCOMP PDX-79738
83607	1,186	PLASTIC THERMOFIL S 30NF0100
83608	1,186	PLASTIC THERMOFIL S 40FG0100
83609	1,186	PLASTIC THERMOFIL T 20NF0100
83610	1,186	PLASTIC THERMOFIL T 30FG0214
83611	1,186	PLASTIC THERMOFIL T 30NF0214
83612	1,186	PLASTIC THERMOFIL T 40FG0100
83613	1,186	PLASTIC THERMOFIL T 40NF0100
83614	1,186	PLASTIC THERMOFIL T 40NG0948
83615	1,186	PLASTIC THERMOFIL T 50CG0940
83616	1,186	PLASTIC THERMOFIL T 50FM0100
83617	1,186	PLASTIC THERMOFIL U 10FG0100
83618	1,186	PLASTIC THERMOFIL V 10FG0100
83619	1,186	PLASTIC THERMOFIL V 20FG0100
83620	1,186	PLASTIC THERMOFIL V 30FG0100
83621	1,187	PLASTIC THERMOFIL W 10FG0100
83622	1,187	PLASTIC THERMOFIL W 30FG0100
83623	1,187	PLASTIC THERMOFIL W 30NF0100
83624	1,187	PLASTIC THERMOFIL W 30NF0214
83625	1,187	PLASTIC THERMOFIL Y 20FG0100
83626	1,187	PLASTIC THERMOFIL Y 20FG0500
83627	1,187	PLASTIC THERMOFIL Y7 9900-6500
83628	258	ADHESIVE THERMOSET 100
83629	258	ADHESIVE THERMOSET 101
83630	259	ADHESIVE THERMOSET 103
83631	259	ADHESIVE THERMOSET 104
83632	259	ADHESIVE THERMOSET 125
83633	259	ADHESIVE THERMOSET 267
83634	259	ADHESIVE THERMOSET DC232
83635	259	ADHESIVE THERMOSET DC80
83636	259	ADHESIVE THERMOSET EP233
83637	259	ADHESIVE THERMOSET EP280

MSFC-HDBK-527 REV F 9999942 0006813 3

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
83638	259	ADHESIVE THERMOSET EP433
83639	259	ADHESIVE THERMOSET EP539
83640	259	ADHESIVE THERMOSET EP548
83641	259	ADHESIVE THERMOSET EP598
83642	105	ADHESIVE EC1137
83643	106	ADHESIVE EC1239 B/A CLASS A 1/2
83644	106	ADHESIVE EC1239 B/A CLASS A 1/4
83645	106	ADHESIVE EC1239 B/A CLASS A 2
83646	106	ADHESIVE EC1239 B/A CLASS A 4
83647	106	ADHESIVE EC1239 B/A CLASS B 1/2
83648	106	ADHESIVE EC1239 B/A CLASS B 1/4
83649	106	ADHESIVE EC1239 B/A CLASS B 2
83650	106	ADHESIVE EC1239 B/A CLASS B 4
83651	237	ADHESIVE SCOTCHSEAL 1792
83652	106	ADHESIVE EC1547 B/A
83653	237	ADHESIVE SCOTCHSEAL 1252
83654	237	ADHESIVE SCOTCHSEAL 1279
83655	238	ADHESIVE SCOTCHSEAL 1814
83656	238	ADHESIVE SCOTCHSEAL 2084
83657	238	ADHESIVE SCOTCHSEAL 2084H
83658	238	ADHESIVE SCOTCHSEAL 612
83659	238	ADHESIVE SCOTCHSEAL 750
83660	238	ADHESIVE SCOTCHSEAL 800
83661	238	ADHESIVE SCOTCHSEAL 801 B/A
83662	238	ADHESIVE SCOTCHWELD 111
83663	238	ADHESIVE SCOTCHWELD 13
83664	238	ADHESIVE SCOTCHWELD 15
83665	238	ADHESIVE SCOTCHWELD 2214 HI DENSITY
83666	239	ADHESIVE SCOTCHWELD 2214 HI FLEX
83667	239	ADHESIVE SCOTCHWELD 2214 NONMETALLIC
83668	239	ADHESIVE SCOTCHWELD 3501 B/A
83669	239	ADHESIVE SCOTCHWELD 3533 B/A
83670	239	ADHESIVE SCOTCHWELD 3553 B/A
83671	239	ADHESIVE SCOTCHWELD 4060
83672	240	ADHESIVE SCOTCHWELD 42
83673	241	ADHESIVE SCOTCHWELD EC3430
83674	277	ADHESIVE WEATHERBAN 202
83675	277	ADHESIVE WEATHERBAN 404
83676	277	ADHESIVE WEATHERBAN 506NF
83677	1,299	RUBBER MBS106
83678	1,299	RUBBER MBS154
83679	1,189	PLASTIC UBE NYLON 1011FB
83680	1,189	PLASTIC UBE NYLON 1011GC4
83681	1,190	PLASTIC UBE NYLON 1013B
83682	1,190	PLASTIC UBE NYLON 1013NB
83683	1,190	PLASTIC UBE NYLON 1013NH
83684	1,190	PLASTIC UBE NYLON 1013NU2
83685	1,190	PLASTIC UBE NYLON 1013NW8
83686	1,190	PLASTIC UBE NYLON 1013R
83687	1,190	PLASTIC UBE NYLON 1013RU1
83688	1,190	PLASTIC UBE NYLON 1013RW
83689	1,190	PLASTIC UBE NYLON 1015G1
83690	1,190	PLASTIC UBE NYLON 1015GC6
83691	1,190	PLASTIC UBE NYLON 1015GC9
83692	1,190	PLASTIC UBE NYLON 10181
83693	1,190	PLASTIC UBE NYLON 1022B
83694	1,190	PLASTIC UBE NYLON 1022SV2
83695	1,191	PLASTIC UBE NYLON 1030B
83696	1,191	PLASTIC UBE NYLON 1030J
83697	1,191	PLASTIC UBE NYLON 1030QB
83698	1,191	PLASTIC UBE NYLON 2015B
83699	1,191	PLASTIC UBE NYLON 2015SV
83700	1,191	PLASTIC UBE NYLON 2020B
83701	1,191	PLASTIC UBE NYLON 2020GC4
83702	1,191	PLASTIC UBE NYLON 2020GC6
83703	1,191	PLASTIC UBE NYLON 2020GC9
83704	1,192	PLASTIC UBE NYLON 3030GCU
83705	1,192	PLASTIC UBE NYLON 3030H
83706	1,191	PLASTIC UBE NYLON 2020U
83707	1,191	PLASTIC UBE NYLON 2020UW1
83708	1,191	PLASTIC UBE NYLON 3014U
83709	1,191	PLASTIC UBE NYLON 3020LU1
83710	1,191	PLASTIC UBE NYLON 3024LU
83711	1,192	PLASTIC UBE NYLON 3024U
83712	1,192	PLASTIC UBE NYLON 3035JL1
83713	1,192	PLASTIC UBE NYLON 3035JU
83714	1,192	PLASTIC UBE NYLON 3035JU6
83715	1,192	PLASTIC UBE NYLON 3035LU
83716	1,192	PLASTIC UBE NYLON 3035U
83717	796	PLASSTIC UBE NYLON 5013B
83718	1,192	PLASTIC UBE NYLON 5033J12
83719	1,192	PLASTIC UBE NYLON UMC1
83720	829	PLASTIC BAKELITE DPD6169 NATURAL
83721	829	PLASTIC BAKELITE DPDA6479 NATURAL
83722	829	PLASTIC BAKELITE DQDA6479 NATURAL 7
83723	829	PLASTIC BAKELITE DQDA6480 NATURAL 7
83724	829	PLASTIC BAKELITE OPDA9169 NATURAL
83725	1,192	PLASTIC UCAR DFDA1137 NATURAL
83726	1,192	PLASTIC UCAR DFDA1138 NATURAL
83727	1,192	PLASTIC UDEL POLYSULFONE P1700 CL2611
83728	859	PLASTIC DFD4960 NATURAL
83729	859	PLASTIC DFD6005 NATURAL
83730	859	PLASTIC DFD6201 NATURAL
83731	856	PLASTIC DBDA0160 NATURAL
83732	859	PLASTIC DFDA0588 BLACK 9865
83733	859	PLASTIC DFDA4964 NATURAL
83734	859	PLASTIC DFDA6059 BLACK 9865
83735	859	PLASTIC DFDA6080 BLACK 4865
83736	860	PLASTIC DFDA6202 NATURAL
83737	860	PLASTIC DFDA6423 BLACK 9865
83738	860	PLASTIC DFDA6425 BLACK 9865
83739	860	PLASTIC DFDA7540 NATURAL
83740	860	PLASTIC DFNF0092 BLACK
83741	860	PLASTIC DGDA2400
83742	860	PLASTIC DGDA2483 BLACK 4865
83743	860	PLASTIC DGDA3485 NATURAL
83744	860	PLASTIC DGDB2480 BLACK 4865
83745	860	PLASTIC DGDB3110 NATURAL
83746	860	PLASTIC DGDJ3364 NATURAL
83747	860	PLASTIC DGDJ3479 BLACK 9865

MSFC-HDBK-527 REV F 9999942 0006814 5

Information Handling Services, 2000

NON-METALS DESIGNATIONS BY MATERIAL CODE

MATCD	PAGE	DESIGNATION
83748	860	PLASTIC DHDA6497 BLACK 9865
83749	861	PLASTIC DHDA7704 BLACK 55
83750	863	PLASTIC DMDA6010 NATURAL
83751	863	PLASTIC DMDA6020 NATURAL 7
83752	863	PLASTIC DMDA6143 NATURAL 7
83753	863	PLASTIC DMDA6145 NATURAL 7
83754	860	PLASTIC DHDA2463 BLACK 4865
83755	863	PLASTIC DMDA6147 NATURAL 7
83756	863	PLASTIC DMDA7154 NATURAL 7UV
83757	863	PLASTIC DMDA8920 NATURAL 7
83758	863	PLASTIC DMDA8940 NATURAL 7
83759	863	PLASTIC DNDA4070 NATURAL 7
83760	864	PLASTIC DNDC7148 NATURAL 7
83761	864	PLASTIC DNDC7150 NATURAL 7
83762	865	PLASTIC DQDA6832 NATURAL 7
83763	922	PLASTIC G RESIN 7144 NATURAL 7
83764	922	PLASTIC G RESIN 7342 NATURAL 7
83765	922	PLASTIC G RESIN 7441 NATURAL 7
83766	922	PLASTIC G RESIN 8007 NATURAL 7
83767	922	PLASTIC G RESIN 8320 NATURAL 7
83768	923	PLASTIC G RESIN 8940 NATURAL 7
83769	927	PLASTIC GPEP1000
83770	927	PLASTIC GPEP703 NATURAL 7
83771	927	PLASTIC GPEP705 NATURAL 7
83772	927	PLASTIC GPEP803 NATURAL 7
83773	927	PLASTIC GPEP805 NATURAL 7
83774	927	PLASTIC GPEP903 BLACK
83775	927	PLASTIC GPEP954 NATURAL 7UV
83776	927	PLASTIC GPSC2704 BLACK
83777	930	PLASTIC GRSN1077 NATURAL 7
83778	930	PLASTIC GRSN7147 NATURAL 7
83779	930	PLASTIC GRSN7149 NATURAL 7
83780	930	PLASTIC GRSN7340 NATURAL 7
83781	930	PLASTIC GRSN7341 NATURAL 7
83782	930	PLASTIC GRSN7510 NATURAL 7
83783	931	PLASTIC GRSN8350 NATURAL 7
83784	931	PLASTIC GRSN8907 NATURAL 7
83785	934	PLASTIC HFDA0580 BLACK 55
83786	934	PLASTIC HFDA0581 BLACK 55
83787	934	PLASTIC HFDA0691 BLACK 55
83788	934	PLASTIC HFDA5612 BLACK 75
83789	934	PLASTIC HFDA5630 BLACK 185
83790	935	PLASTIC HFDA6522 NATURAL
83791	935	PLASTIC HFDE4201 NATURAL EC
83792	1,218	PLASTIC USS C040Y
83793	1,219	PLASTIC USS C120Y
83794	1,219	PLASTIC USS C432-12
83795	1,219	PLASTIC USS C432-4
83796	1,219	PLASTIC USS CP350A
83797	1,219	PLASTIC USS CP450A
83798	1,219	PLASTIC USS CR080A
83799	1;219	PLASTIC USS CRVO-8
83800	1,219	PLASTIC USS D007W
83801	1,219	PLASTIC USS F007
83802	1,219	PLASTIC USS F010M
83803	1,219	PLASTIC USS F012
83804	1,219	PLASTIC USS F012M
83805	1,219	PLASTIC USS F015
83806	1,219	PLASTIC USS F040F
83807	1,220	PLASTIC USS F080F
83808	1,220	PLASTIC USS F080L
83809	1,220	PLASTIC USS F1202L
83810	1,220	PLASTIC USS F120F
83811	1,220	PLASTIC USS F120L
83812	1,220	PLASTIC USS FP120F
83813	1,220	PLASTIC USS FP200F
83814	1,220	PLASTIC USS FP300F
83815	1,220	PLASTIC USS FP330W
83816	1,220	PLASTIC USS FPT120F
83817	1,220	PLASTIC USS FPT180F
83818	1,220	PLASTIC USS FPT230F
83819	1,220	PLASTIC USS FPT350F
83820	1,220	PLASTIC USS FT040W
83821	1,221	PLASTIC USSS FT080W
83822	1,221	PLASTIC USS FT120C
83823	1,221	PLASTIC USS FT120W
83824	1,221	PLASTIC USS FT120W2L
83825	1,221	PLASTIC USS FT120WB
83826	1,221	PLASTIC USS FT145V
83827	1,221	PLASTIC USS L040G
83828	1,221	PLASTIC USS T14025G
83829	1,221	PLASTIC USS T14040G
83830	1,221	PLASTIC USS T14070G
83831	1,221	PLASTIC USS T14230G
83832	1,221	PLASTIC USS T15035G
83833	1,221	PLASTIC USS T15230G
83834	1,282	RUBBER EPOXICAL 840A
83835	1,282	RUBBER EPOXICAL 885A
83836	1,000	PLASTIC NORCHEM 1028
83837	1,000	PLASTIC NORCHEM 1028A
83838	1,000	PLASTIC NORCHEM 3010
83839	1,000	PLASTIC NORCHEM 3023
83840	1,000	PLASTIC NORCHEM 3025
83841	1,001	PLASTIC NORCHEM 3029
83842	1,001	PLASTIC NORCHEM 3414
83843	1,001	PLASTIC NORCHEM 5164
83844	1,001	PLASTIC NORCHEM 5174
83845	1,001	PLASTIC NORCHEM 5304T
83846	1,001	PLASTIC NORCHEM 5305T
83847	1,001	PLASTIC NORCHEM 5307
83848	1,001	PLASTIC NORCHEM 5310T
83849	1,000	PLASTIC NORCHEM
83850	1,001	PLASTIC NORCHEM 6462HR
83851	1,001	PLASTIC NORCHEM 820
83852	1,001	PLASTIC NORCHEM 831
83853	1,001	PLASTIC NORCHEM 836
83854	1,001	PLASTIC NORCHEM 8404HJ
83855	1,001	PLASTIC NORCHEM 8410ZR
83856	1,002	PLASTIC NORCHEM 853
83857	1,002	PLASTIC NORCHEM 860

MSFC-HDBK-527 REV F 9999942 0006815 7

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
83858	1,002	PLASTIC NORCHEM HND 5903
83859	1,002	PLASTIC NORCHEM NHD 5905
83860	1,002	PLASTIC NORCHEM NHD 6905
83861	1,002	PLASTIC NORCHEM NHD6908
83862	1,002	PLASTIC NORCHEM NPE 130
83863	1,002	PLASTIC NORCHEM NPE 190
83864	1,002	PLASTIC NORCHEM NPE 191
83865	1,002	PLASTIC NORCHEM NPE 195
83866	1,002	PLASTIC NORCHEM NPE 210
83867	1,002	PLASTIC NORCHEM NPE 253
83868	1,002	PLASTIC NORCHEM NPE 265
83869	1,002	PLASTIC NORCHEM NPE 283
83870	1,003	PLASTIC NORCHEM NPE 293
83871	1,003	PLASTIC NORCHEM NPE 3801
83872	1,003	PLASTIC NORCHEM NPE 3855
83873	1,003	PLASTIC NORCHEM NPE 3865
83874	1,003	PLASTIC NORCHEM NPE 510
83875	1,003	PLASTIC NORCHEM NPE 510-3
83876	1,003	PLASTIC NORCHEM NPP 1602WF
83877	994	PLASTIC MICROTHENE MA778
83878	994	PLASTIC MICROTHENE MA795
83879	994	PLASTIC MICROTHENE MA795-15
83880	994	PLASTIC MICROTHENE MC81035
83881	994	PLASTIC MICROTHENE MC91381
83882	994	PLASTIC MICROTHENE MK91010
83883	994	PLASTIC MICROTHENE MK91018
83884	995	PLASTIC MICROTHENE MN710-20
83885	995	PLASTIC MICROTHENE MN711-20
83886	995	PLASTIC MICROTHENE MN718
83887	995	PLASTIC MICROTHENE MN720-38
83888	994	PLASTIC MICROTHENE MN 722
83889	995	PLASTIC MICROTHENE MP732-16
83890	995	PLASTIC MICROTHENE MP736-16
83891	994	PLASTIC MICROTHENE MP744-16
83892	995	PLASTIC MICROTHENE MU760 19% VA
83893	995	PLASTIC MICROTHENE MU763 9% VA
83894	1,035	PLASTIC PETROTHENE FM704
83895	1,035	PLASTIC PETROTHENE FR412
83896	1,035	PLASTIC PETROTHENE FR424
83897	1,035	PLASTIC PETROTHENE FX702
83898	1,035	PLASTIC PETROTHENE FX703
83899	1,035	PLASTIC PETROTHENE FX705
83900	1,035	PLASTIC PETROTHENE KR21017
83901	1,035	PLASTIC PETROTHENE KR901028
83902	1,035	PLASTIC PETROTHENE KR92561
83903	1,034	PLASTIC PETOTHENE KR92562
83904	1,035	PLASTIC PETROTHENE LB710
83905	1,035	PLASTIC PETROTHENE LB742
83906	1,036	PLASTIC PETROTHENE LB830
83907	1,036	PLASTIC PETROTHENE LB832
83908	1,036	PLASTIC PETROTHENE LC732
83909	1,036	PLASTIC PETROTHENE LR734
83910	1,036	PLASTIC PETROTHENE LR920
83911	1,036	PLASTIC PETROTHENE LR580
83912	1,036	PLASTIC PETROTHENE LR586
83913	1,038	PLASTIC PETROTHENE NA171
83914	1,038	PLASTIC PETROTHENE NA301
83915	1,038	PLASTIC PETROTHENE NA301-06
83916	1,038	PLASTIC PETROTHENE NA307
83917	1,038	PLASTIC PETROTHENE NA309
83918	1,038	PLASTIC PETROTHENE NA310-05
83919	1,039	PLASTIC PETROTHENE NA310-06
83920	1,039	PLASTIC PETROTHENE XL3512
83921	1,039	PLASTIC PETROTHENE XL3700
83922	1,039	PLASTIC PETROTHENE XL5421
83923	1,039	PLASTIC PETROTHENE XL5422
83924	1,039	PLASTIC PETROTHENE XL5423
83925	1,039	PLASTIC PETROTHENE XL5461
83926	1,039	PLASTIC PETROTHENE XL5482
83927	1,039	PLASTIC PETROTHENE XL5483
83928	1,039	PLASTIC PETROTHENE XL5484
83929	1,039	PLASTIC PETROTHENE XL5485
83930	1,039	PLASTIC PETROTHENE XL5486
83931	1,039	PLASTIC PETROTHENE XL5487
83932	1,039	PLASTIC PETROTHENE XL7400
83933	1,040	PLASTIC PETROTHENE XL7403
83934	1,040	PLASTIC PETROTHENE XL7410
83935	1,040	PLASTIC PETROTHENE XL7411
83936	1,040	PLASTIC PETROTHENE YR190505
83937	1,040	PLASTIC PETROTHENE YR19512
83938	1,040	PLASTIC PETROTHENE YR92126
83939	1,040	PLASTIC PETROTHENE YR92273
83940	1,040	PLASTIC PETROTHENE YR92411
83941	1,200	PLASTIC ULTRATHENE UE634 28% VA
83942	1,200	PLASTIC ULTRATHENE UE645 28% VA
83943	1,200	PLASTIC ULTRATHENE UE648 19% VA
83944	1,200	PLASTIC ULTRATHENE UE656-03 12% VA
83945	1,200	PLASTIC ULTRATHENE UE658 12% VA
83946	1,200	PLASTIC ULTRATHENE UE630 17% VA
83947	810	PLASTIC ABSG1FG2
83948	1,032	PLASTIC PE25
83949	1,032	PLASTIC PE2FR
83950	1,033	PLASTIC PE3CC3
83951	1,033	PLASTIC PE47MF1
83952	1,076	PLASTIC PP1MT3
83953	1,072	PLASTIC PP-C2TF4
83954	1,072	PLASTIC PP-C3CC4
83955	1,072	PLASTIC PP-C3TF2
83956	1,072	PLASTIC PP-C4IM-V
83957	1,073	PLASTIC PP-C5CC2
83958	1,073	PLASTIC PP-C6CC4
83959	1,073	PLASTIC PP-H1CC1
83960	1,073	PLASTIC PP-H2CC2
83961	1,073	PLASTIC PP-H2LTF4
83962	1,073	PLASTIC PP-H2MFQ3
83963	1,073	PLASTIC PP-H2MFQ4
83964	1,073	PLASTIC PP-H2MFS3
83965	1,073	PLASTIC PP-H2MFS4
83966	1,073	PLASTIC PP-H2TF2
83967	1,073	PLASTIC PP-H3MF2

MSFC-HDBK-527 REV F 9999942 0006816 9

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
83968	1,073	PLASTIC PP-H3MF05
83969	1,073	PLASTIC PP-H4CG4
83970	1,073	PLASTIC PP-H4TF3
83971	1,074	PLASTIC PP-H6CC4
83972	1,074	PLASTIC PP-H7CC4
83973	1,074	PLASTIC PP-HFG1
83974	1,074	PLASTIC PP-HFG2
83975	1,074	PLASTIC PP-HFG3
83976	1,074	PLASTIC PP-HFGC2
83977	1,074	PLASTIC PP-HFGC3
83978	1,074	PLASTIC PP-HIFR
83979	1,074	PLASTIC PP-TFFR2
83980	1,224	PLASTIC VB511
83981	1,230	PLASTIC WELLAMID 210N
83982	1,230	PLASTIC WELLAMID 21L-N
83983	1,230	PLASTIC WELLAMID 21LH-N
83984	1,230	PLASTIC WELLAMID 21LN2-NNT
83985	1,230	PLASTIC WELLAMID 21U-NBK1
83986	1,230	PLASTIC WELLAMID 220N
83987	1,230	PLASTIC WELLAMID 22L-N
83988	1,230	PLASTIC WELLAMID 22LH-N
83989	1,230	PLASTIC WELLAMID 22LH13XE-N
83990	1,230	PLASTIC WELLAMID 22LH14XE-N
83991	1,230	PLASTIC WELLAMID 22LH15XE-N
83992	1,231	PLASTIC WELLAMID 33LH16XE-N
83993	1,230	PLASTIC WELLAMID 22LN2-N
83994	1,231	PLASTIC WELLAMID 420N
83995	1,231	PLASTIC WELLAMID 420XE-N
83996	1,231	PLASTIC WELLAMID 42L-N
83997	1,231	PLASTIC WELLAMID 42L-XE-N
83998	1,091	PLASTIC PROLOY HC3
83999	54	ADHESIVE BOSTIK 320
84000	55	ADHESIVE BOSTIK 620
84001	56	ADHESIVE BOSTIK 920
84002	54	ADHESIVE BOSTIK 2000
84003	54	ADHESIVE BOSTIK 3000
84004	54	ADHESIVE BOSTIK 4000
84005	56	ADHESIVE BOSTIK 9732
84006	1,271	RUBBER BOYD NR35
84007	1,271	RUBBER BOYD OR50
84008	1,271	RUBBER BOYD OR60
84009	1,271	RUBBER BOYD OR70
84010	1,272	RUBBER BUNA N NBR50
84011	1,272	RUBBER BUNA N NBR60
84012	1,272	RUBBER BUNA N NBR70
84013	1,272	RUBBER BUNA S SBR75
84014	1,273	RUBBER BUTYL IIR55
84015	1,285	RUBBER EPT60
84016	1,302	RUBBER NEOPRENE CR45
84017	1,302	RUBBER NEOPRENE CR50
84018	1,302	RUBBER NEOPRENE CR60
84019		DELETED SEE 64064
84020	1,302	RUBBER NEOPRENE CR MC
84021	1,360	RUBBER SILICONE SI400
84022	1,360	RUBBER SILICONE SI500
84023	1,175	PLASTIC THERMOCOMP ZF-1004
84024	1,175	PLASTIC THERMOCOMP ZF-1006
84025	1,176	PLASTIC THERMOCOMP ZF-1008
84026	1,224	PLASTIC VERTON RF-700-10
84027	1,224	PLASTIC VERTON RF-700-1EM
84028	1,224	PLASTIC VERTON RF-7003FR
84029	1,224	PLASTIC VERTON RF-7006
84030	1,224	PLASTIC VERTON RF-7006EM
84031	1,224	PLASTIC VERTON RF-7006FR
84032	1,225	PLASTIC VICTREX PEEK 450CA30
84033	1,225	PLASTIC VICTREX PEEK 450G
84034	1,225	PLASTIC VICTREX PEEK 450GL30
84035	1,225	PLASTIC VICTREX PEEK D150CA30
84036	1,226	PLASTIC VICTREX PEEK D150GL30
84037	1,226	PLASTIC VICTREX PES 4100G
84038	1,226	PLASTIC VICTREX PES 4101GL20
84039	1,226	PLASTIC VICTREX PES 410GL30
84040	1,226	PLASTIC VICTREX PES D4800HF30
84041	1,226	PLASTIC VICTREX PES D4800HL15
84042	1,170	PLASTIC THERMOCOMP PDX-81319
84043	1,170	PLASTIC THERMOCOMP PF-100-10
84044	1,170	PLASTIC THERMOCOMP PF-100-12
84045	1,170	PLASTIC THERMOCOMP PF-1002
84046	1,170	PLASTIC THERMOCOMP PF-1002HI
84047	1,171	PLASTIC THERMOCOMP PF-1004
84048	1,171	PLASTIC THERMOCOMP PF-1004HI
84049	1,171	PLASTIC THERMOCOMP PF-1006
84050	1,171	PLASTIC THERMOCOMP PF-1006HI
84051	1,171	PLASTIC THERMOCOMP PF-1006FR
84052	1,171	PLASTIC THERMOCOMP PF-1008
84053	1,171	PLASTIC THERMOCOMP PF-1008HI
84054	1,171	PLASTIC THERMOCOMP PFL-4216
84055	1,171	PLASTIC THERMOCOMP PFL-4218
84056	1,171	PLASTIC THERMOCOMP QC-1006
84057	1,171	PLASTIC THERMOCOMP QF-100-10
84058	1,171	PLASTIC THERMOCOMP QF-100-12
84059	1,171	PLASTIC THERMOCOMP QF-1002
84060	1,171	PLASTIC THERMOCOMP QF-1004
84061	1,172	PLASTIC THERMOCOMP QF-1006
84062	1,172	PLASTIC THERMOCOMP QF-1006FR
84063	1,172	PLASTIC THERMOCOMP QF-1008
84064	1,172	PLASTIC THERMOCOMP R1000 FR HS
84065	1,172	PLASTIC THERMOCOMP R1000 FR
84066	1,172	PLASTIC THERMOCOMP RC-1002
84067	1,172	PLASTIC THERMOCOMP RC-1004
84068	176	ADHESIVE IMPRUV 349
84069	176	ADHESIVE IMPRUV 365
84070	176	ADHESIVE IMPRUV 366
84071	205	ADHESIVE OUTPUT 315
84072	205	ADHESIVE OUTPUT 383
84073	205	ADHESIVE OUTPUT 384
84074	228	ADHESIVE RAILSAFE ENGINE SEAL 12336
84075	254	ADHESIVE SUPERBONDER 409
84077	905	PLASTIC FASTOOL RP3265
84078	1,103	PLASTIC RP-1220

MSFC-HDBK-527 REV F 9999942 0006817 0

Information Handling Services, 2000

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
84079	1,103	PLASTIC RP-1225
84080	1,103	PLASTIC RP-1710
84081	1,104	PLASTIC RP-1720
84082	1,104	PLASTIC RP-1774
84083	1,105	PLASTIC RP306
84084	1,172	PLASTIC THERMOCOMP RC-1006
84085	1,104	PLASTIC RP-3209-1
84086	1,104	PLASTIC RP-3209-2
84087	1,104	PLASTIC RP-3215-1
84088	1,172	PLASTIC THERMOCOMP RC-1006HI
84089	1,104	PLASTIC RP-3215-2
84090	1,172	PLASTIC THERMOCOMP RC-1006PC
84091	1,104	PLASTIC RP-3215-3
84092	1,172	PLASTIC THERMOCOMP RC-1008
84093	1,172	PLASTIC THERMOCOMP RCL-4036
84094	1,172	PLASTIC THERMOCOMP RCL-4536
84095	1,172	PLASTIC THERMOCOMP RF-100-10
84096	1,173	PLASTIC THERMOCOMP RF-100-12
84097	1,173	PLASTIC THERMOCOMP RF-1002
84098	1,173	PLASTIC THERMOCOMP RF-1002HI
84099	1,173	PLASTIC THERMOCOMP RF-1004
84100	1,173	PLASTIC THERMOCOMP RF-1004HI
84101	1,173	PLASTIC THERMOCOMP RF-1004FR
84102	1,173	PLASTIC THERMOCOMP RF-1004FR HS
84103	1,173	PLASTIC THERMOCOMP RF-1006
84104	1,173	PLASTIC THERMOCOMP RF-1006HI
84105	1,173	PLASTIC THERMOCOMP RF-1006FR
84106	1,173	PLASTIC THERMOCOMP RF-1008
84107	1,173	PLASTIC THERMOCOMP RF-1008HI
84108	1,173	PLASTIC THERMOCOMP RFL-4216
84109	1,173	PLASTIC THERMOCOMP RFL-4218
84110	1,174	PLASTIC THERMOCOMP RL-4310
84111	1,104	PLASTIC RP-3261
84112	1,104	PLASTIC RP-3253
84113	1,167	PLASTIC THERMOCOMP FS-100-10
84114	1,174	PLASTIC THERMOCOMP SF-1006
84115	1,174	PLASTIC THERMOCOMP STAT-KON D
84116	1,104	PLASTIC RP-3262
84117	1,174	PLASTIC THERMOCOMP STYPRENIC
84118	1,104	PLASTIC RP-3266 45/55
84119	1,174	PLASTIC THERMOCOMP UF-1006
84120	1,104	PLASTIC RP-3266 5-/45
84121	1,295	RUBBER KALREZ 3018
84122	1,104	PLASTIC RP-3266 50/50
84123	1,174	PLASTIC THERMOCOMP UNFORTIFIED NYLON 6/10
84124	1,104	PLASTIC RP-3269
84125	1,174	PLASTIC THERMOCOMP UNFORTIFIED NYLON 11
84126	1,105	PLASTIC RP-3269-1
84127	1,174	PLASTIC THERMOCOMP UNFORTIFIED NYLON 12
84128	1,105	PLASTIC RP-3270 CASTING
84129	1,174	PLASTIC THERMOCOMP UNFORTIFIED NYLON 6
84130	1,105	PLASTIC RP-3270 LAMINATING
84131	1,174	PLASTIC THERMOCOMP UNFORTIFIED NYLON 6/12
84132	1,105	PLASTIC RP-4005/1500H
84133	1,174	PLASTIC THERMOCOMP UNFORTIFIED NYLON 6/6
84134	1,174	PLASTIC THERMOCOMP VC-1006
84135	1,174	PLASTIC THERMOCOMP WC-1006
84136	1,174	PLASTIC THERMOCOMP WF-1002
84137	1,175	PLASTIC THERMOCOMP WF-1002HI
84138	1,105	PLASTIC RP-4003
84139	1,175	PLASTIC THERMOCOMP WF-1004
84140	1,175	PLASTIC THERMOCOMP WF-1004HI
84141	1,175	PLASTIC THERMOCOMP WF-1006
84142	1,175	PLASTIC THERMOCOMP WF-1006HI
84143	1,175	PLASTIC THERMOCOMP WF-1006FR
84144	1,329	RUBBER SILICONE CHOSEAL 1220
84145	1,175	PLASTIC THERMOCOMP WF-1008
84146	1,175	PLASTIC THERMOCOMP WF-1008HI
84147	1,175	PLASTIC THERMOCOMP XC-1006
84148	1,175	PLASTIC THERMOCOMP XF-1004
84149	1,175	PLASTIC THERMOCOMP XF-1006
84150	1,175	PLASTIC THERMOCOMP XFL-4036
84151	1,329	RUBBER SILICONE CHOSEAL 1287
84152	1,329	RUBBER SILICONE CHOSEAL 1350
84153	873	PLASTIC DYNAMOLD MS26
84154	1,329	RUBBER SILICONE CHOSEAL 1401
84155	1,329	RUBBER SILICONE CHOSEAL 1485
84156	873	PLASTIC DYNAMOLD DMS4-828
84157	1,329	RUBBER SILICONE CHOTHERM 1641
84158	1,329	RUBBER SILICONE CHOTHERM 1642
84159	1,330	RUBBER SILICONE CHOTHERM 1665
84160	1,330	RUBBER SILICONE CHOTHERM 1666
84161	1,330	RUBBER SILICONE CHOTHERM 1667
84162	870	PLASTIC DUREZ 29429
84163	1,276	RUBBER COHRLASTIC 300
84164	1,276	RUBBER COHRLASTIC 400
84165	1,277	RUBBER COHRLASTIC 500
84166	1,277	RUBBER COHRLASTIC 600
84167	1,277	RUBBER COHRLASTIC 9030
84168	1,277	RUBBER COHRLASTIC 9040
84169	1,277	RUBBER COHRLASTIC 9050
84170	1,278	RUBBER COHRLASTIC 9070
84171	985	PLASTIC MC2100
84172	985	PLASTIC MC3100
84173	985	PLASTIC MC3500
84174	985	PLASTIC MC3600
84175	985	PLASTIC MC3700
84176	985	PLASTIC MC5161
84177	849	PLASTIC COMALLOY 710-3040
84178	985	PLASTIC MC6561
84179	985	PLASTIC MC6800
84180	985	PLASTIC MC9540
84181	849	PLASTIC COMALLOY HILOY 610
84182	985	PLASTIC MD9520
84183	1,029	PLASTIC PE 1007
84184	1,029	PLASTIC PE 1008.5
84185	1,032	PLASTIC PE1117A
84186	1,029	PLASTIC PE 117A
84187	1,029	PLASTIC PE 1205
84188	1,029	PLASTIC PE 1207

MSFC-HDBK-527 REV F 9999942 0006818 2

MATCD	PAGE	DESIGNATION
84189	1,030	PLASTIC PE 1220
84190	1,030	PLASTIC PE 1260
84191	1,030	PLASTIC PE 1400
84192	1,030	PLASTIC PE 1408.5
84193	1,030	PLASTIC PE 1409
84194	1,030	PLASTIC PE 1412
84195	1,032	PLASTIC PE 4538A
84196	1,032	PLASTIC PE 4538B
84197	1,032	PLASTIC PE 5104
84198	1,275	RUBBER CHOFOAM 1501
84199	875	PLASTIC EA6740
84200	875	PLASTIC EA6750
84201	875	PLASTIC EA6765
84202	876	PLASTIC EA9400
84203	876	PLASTIC EB6780
84204	876	PLASTIC EC2100
84205	876	PLASTIC EC6600
84206	876	PLASTIC EC6760
84207	876	PLASTIC EC6770
84208	880	PLASTIC EH6600
84209	935	PLASTIC HID9112
84210	935	PLASTIC HID9114
84211	935	PLASTIC HID9116
84212	935	PLASTIC HID9122
84213	935	PLASTIC HID9402
84214	935	PLASTIC HID9406
84215	935	PLASTIC HID9410
84216	935	PLASTIC HID9412/9413
84217	935	PLASTIC HID9416
84218	935	PLASTIC HID9450
84219	935	PLASTIC HID9512/9513
84220	950	PLASTIC KN220
84221	950	PLASTIC KN226
84222	950	PLASTIC KN230
84223	980	PLASTIC MA3200
84224	980	PLASTIC MA5000
84225	980	PLASTIC MA9000
84226	980	PLASTIC MA6800
84227	1,018	PLASTIC NYLON 1003-4
84228	773	MOLD COMPOUND RYTON R-5
84229	1,295	RUBBER KALREZ 3065
84230	1,375	RUBBER VITON E46315
84231	893	PLASTIC EP5182
84232	893	PLASTIC EP5282
84233	893	PLASTIC EPBGC78-3
84234	896	PLASTIC EPSL166
84235	896	PLASTIC EPSL174
84236	1,307	RUBBER NITRILE GRADE 50
84237	1,307	RUBBER NITRILE GRADE 60
84238	1,307	RUBBER NITRILE GRADE 70
84239	1,307	RUBBER NITRILE GRADE 80
84240	1,331	RUBBER SILICONE CL 1A & 1B GR 60
84241	1,331	RUBBER SILICONE CL 1A & 1B GR 70
84242	798	PLASTIC 224
84243	801	PLASTIC 306

MATCD	PAGE	DESIGNATION
84244	856	PLASTIC D33
84245	856	PLASTIC D44
84246	856	PLASTIC D45
84247	856	PLASTIC D62
84248	856	PLASTIC D62CM
84249	856	PLASTIC D63
84250	856	PLASTIC D69
84251	856	PLASTIC D72
84252	856	PLASTIC D73
84253	856	PLASTIC D73F
84254	874	PLASTIC E484
84255	874	PLASTIC E486
84256	874	PLASTIC E487
84257	874	PLASTIC E4905
84258	874	PLASTIC E4920
84259	874	PLASTIC E4930
84260	852	PLASTIC CTI NYLON 6/6 NN60CF
84261	852	PLASTIC CTI NYLON 6/6 NN60GF
84262	852	PLASTIC CTI PEEK PK20CF/000
84263	852	PLASTIC CTI POLYSULFONE PF30F/15T
84264	852	PLASTIC CTI SAN SN20GF
84265	853	PLASTIC CTI SAN SN30GF
84266	853	PLASTIC CTI SAN SN40GF
84267	1,248	POTTING COMPOUND CONATHANE TU960
84268	1,245	POTTING COMPOUND CONATHANE DPEN8536
84269	1,245	POTTING COMPOUND CONATHANE EN10
84270	1,245	POTTING COMPOUND CONATHANE EN11
84271	1,245	POTTING COMPOUND CONATHANE EN12
84272		DELETED SEE 80069
84273	1,246	POTTING COMPOUND CONATHANE EN20
84274	1,246	POTTING COMPOUND CONATHANE EN21
84275	1,246	POTTING COMPOUND CONATHANE EN2523
84276	1,246	POTTING COMPOUND CONATHANE EN2524
84277	1,246	POTTING COMPOUND CONATHANE EN2525
84278	1,246	POTTING COMPOUND CONATHANE EN2526
84279	1,246	POTTING COMPOUND CONATHANE EN2527
84280	1,246	POTTING COMPOUND CONATHANE EN2528
84281		DELETED SEE 05784
84282	1,247	POTTING COMPOUND CONATHANE EN5
84283	1,247	POTTING COMPOUND CONATHANE EN6
84284	1,247	POTTING COMPOUND CONATHANE EN7
84285	1,247	POTTING COMPOUND CONATHANE EN8
84286	1,247	POTTING COMPOUND CONATHANE EN9
84287	1,247	POTTING COMPOUND CONATHANE EN9 (OZR)
84288	1,248	POTTING COMPOUND CONATHANE UC17
84289	1,249	POTTING COMPOUND CONATHANE UC30
84290	1,249	POTTING COMPOUND CONATHANE UC31
84291	1,249	POTTING COMPOUND CONATHANE UC32
84292	1,249	POTTING COMPOUND CONATHANE UC33
84293	1,249	POTTING COMPOUND CONATHANE UC34
84294	1,246	POTTING COMPOUND CONATHANE EN23
84295	1,246	POTTING COMPOUND CONATHANE EN24
84296	1,247	POTTING COMPOUND CONATHANE EN30
84297	1,247	POTTING COMPOUND CONATHANE TU4010
84298	850	PLASTIC CONAPOXY TE1257/EA071

MSFC-HDBK-527 REV F 9999942 0006819 4

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
84299	850	PLASTIC CONAPOXY TE1257/EA08
84300	850	PLASTIC CONAPOXY TE1257/EA113
84301	850	PLASTIC CONAPOXY TE1257/EA116
84302	850	PLASTIC CONAPOXY TE1257/EA117
84303	1,246	POTTING COMPOUND CONATHANE EN22
84304	1,246	POTTING COMPOUND CONATHANE EN2541
84305	1,246	POTTING COMPOUND CONATHANE EN2543
84306	1,247	POTTING COMPOUND CONATHANE EN2545
84307	1,247	POTTING COMPOUND CONATHANE EN2547
84308	1,247	POTTING COMPOUND CONATHANE EN2548
84309	1,247	POTTING COMPOUND CONATHANE TU400
84310	1,248	POTTING COMPOUND CONATHANE TU500
84311	1,248	POTTING COMPOUND CONATHANE TU50A
84312	1,248	POTTING COMPOUND CONATHANE TU600
84313	1,248	POTTING COMPOUND CONATHANE TU65A
84314	1,248	POTTING COMPOUND CONATHANE TU700
84315	1,248	POTTING COMPOUND CONATHANE TU79
84316	1,248	POTTING COMPOUND CONATHANE TU80
84317	1,248	POTTING COMPOUND CONATHANE TU800
84318	1,248	POTTING COMPOUND CONATHANE TU89
84319	1,248	POTTING COMPOUND CONATHANE TU900
84320	1,248	POTTING COMPOUND CONATHANE TU955
84321	1,248	POTTING COMPOUND CONATHANE UC21
84322	1,249	POTTING COMPOUND CONATHANE UC22
84323	1,249	POTTING COMPOUND CONATHANE UC23
84324	1,249	POTTING COMPOUND CONATHANE UC24
84325	1,249	POTTING COMPOUND CONATHANE UC25
84326	1,249	POTTING COMPOUND CONATHANE UC26
84327	1,249	POTTING COMPOUND CONATHANE UC27
84328	1,249	POTTING COMPOUND CONATHANE UF3
84329	1,250	POTTING COMPOUND EASYPOXY K230
84330	116	ADHESIVE ECN1299/906/MNDMA
84331	129	ADHESIVE EPN1139/HT907/DY062
84332	1,105	PLASTIC RP1118
84333	1,105	PLASTIC RP1125
84334	1,105	PLASTIC RP1126
84335	1,105	PLASTIC RP1129
84336	1,105	PLASTIC RP1700
84337	1,105	PLASTIC RP3260
84338	1,106	PLASTIC RP4018R/RP1520H
84339	1,106	PLASTIC RP4026/RP1501
84340	1,200	PLASTIC UNICHEM 1010G015
84341	1,200	PLASTIC UNICHEM 1011G05
84342	1,200	PLASTIC UNICHEM 1015G015
84343	1,201	PLASTIC UNICHEM 1304-02
84344	1,203	PLASTIC UNICHEM 4261-40
84345	1,205	PLASTIC UNICHEM 5611
84346	1,208	PLASTIC UNICHEM 7090B
84347	1,213	PLASTIC UNICHEM 8091
84348	1,213	PLASTIC UNICHEM 8099
84349	852	PLASTIC CTI ABS AS10GF
84350	852	PLASTIC CTI ABS AS20GF
84351	852	PLASTIC CTI ABS AS30GF
84352	852	PLASTIC CTI ABS AS40GF
84353	1,296	RUBBER KR2001
84354	1,296	RUBBER KR2006
84355	1,296	RUBBER KR2501
84356	1,296	RUBBER KR2502
84357	1,296	RUBBER KR2503
84358	1,296	RUBBER KR2504
84359	1,296	RUBBER KR2601
84360	1,296	RUBBER KR2602
84361	1,296	RUBBER KR2603
84362	1,296	RUBBER KR2604
84363	1,296	RUBBER KR2605
84364	1,296	RUBBER KR2606
84365	1,296	RUBBER KR2621
84366	1,297	RUBBER KR2622
84367	1,297	RUBBER KR2623
84368	1,297	RUBBER KR3001
84369	1,297	RUBBER KR3002
84370	1,297	RUBBER KR3003
84371	1,297	RUBBER KR3004
84372	1,297	RUBBER KR3502
84373	1,297	RUBBER KR3503
84374	1,297	RUBBER KR3504
84375	1,297	RUBBER KR3601
84376	1,297	RUBBER KR3602
84377	1,297	RUBBER KR3603
84378	1,297	RUBBER KR3604
84379	1,297	RUBBER KR3605
84380	1,298	RUBBER KR3606
84381	1,298	RUBBER KR3621
84382	1,298	RUBBER KR3622
84383	1,298	RUBBER KR3623
84384	1,298	RUBBER KR4002
84385	1,298	RUBBER KR4003
84386	1,298	RUBBER KR4004
84387	1,298	RUBBER KR5002
84388	1,298	RUBBER KR5003
84389	1,298	RUBBER KR5004
84390	1,298	RUBBER KR9002
84391	1,307	RUBBER NITRILE GRADE 30
84392	1,307	RUBBER NITRILE GRADE 40
84393	949	PLASTIC K77
84394	948	PLASTIC K31
84395	948	PLASTIC K43
84396	949	PLASTIC K61
84397	949	PLASTIC K66
84398	82	ADHESIVE CRYOSEAL 2132
84399	82	ADHESIVE CRYOSEAL 605
84400	82	ADHESIVE CREST 837
84401	1,061	PLASTIC POLYPENCO 25% GLASS FILLED TFE
84402	1,061	PLASTIC POLYPENCO FLUOROSINT 207
84403	1,061	PLASTIC POLYPENCO FLUOROSINT 500
84404	1,062	PLASTIC POLYPENCO TFE FLUOROCARBON
84405	1,020	PLASTIC NYLON 406
84406	1,091	PLASTIC PS102-0
84407	1,091	PLASTIC PS102-1
84408	1,091	PLASTIC PS108-1

MSFC-HDBK-527 REV F 9999942 0006820 0

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
84409	1,092	PLASTIC PS118-1
84410	1,092	PLASTIC PS202
84411	1,092	PLASTIC PS208
84412	1,092	PLASTIC PS304
84413	1,092	PLASTIC PS308
84414	833	PLASTIC CADCO ABS NATURAL
84415	833	PLASTIC CADCO ACRYLIC PMM CAST
84416	833	PLASTIC CADCO LEXAN POLYCARBONATE EXTRUDED
84417	833	PLASTIC CADCO POLYPROPYLENE NATURAL
84418	834	PLASTIC CADCO POLYSTYRENE HI-IMPACT
84419	834	PLASTIC CADCO PVC RIGID
84420	834	PLASTIC CADCO TEFLON PTFE VIRGIN
84421	857	PLASTIC DELRIN 150
84422	858	PLASTIC DELRIN 550
84423	60	ADHESIVE CADCO BA400
84424	60	ADHESIVE CADCO BA500
84425	60	ADHESIVE CADCO PS18
84426	60	ADHESIVE CADCO PS30
84427	859	PLASTIC DEVCON WET SURFACE REPAIR PUTTY
84428	880	PLASTIC EK40
84429	876	PLASTIC ECCOFOAM PS
84430	876	PLASTIC ECCOGEL 1365
84431	876	PLASTIC ECCOGEL 1365-12
84432	876	PLASTIC ECCOGEL 1365-25
84433	876	PLASTIC ECCOGEL 1365-35
84434	876	PLASTIC ECCOGEL 1365-45
84435	876	PLASTIC ECCOGEL 1365-65
84436	876	PLASTIC ECCOGEL 1365-80
84437	877	PLASTIC ECCOGEL 1365-9
84438	877	PLASTIC ECCOGEL 1365-90
84439	113	ADHESIVE ECCOLITE 82EP-PB
84440	113	ADHESIVE ECCOLITE 82SI-RS
84441	877	PLASTIC ECCOSEAL 1207
84442	877	PLASTIC ECCOSEAL W67
84443	877	PLASTIC ECCOSEAL W19
84444	877	PLASTIC ECCOSEAL W28G
84445	877	PLASTIC ECCOSHIELD CLV
84446	877	PLASTIC ECCOSHIELD SV
84447	114	ADHESIVE ECCOSHIELD VY81
84448	114	ADHESIVE ECCOSHIELD VY-NC
84449	114	ADHESIVE ECCOSHIELD VY-NN
84450	114	ADHESIVE ECCOSIL 1745
84451	114	ADHESIVE ECCOSIL 4553 RUBBER
84452	114	ADHESIVE ECCOSIL 4640
84453	114	ADHESIVE ECCOSIL 4850
84454	115	ADHESIVE ECCOSIL GEL
84455	115	ADHESIVE ECCOSIL TP50
84456	1,281	RUBBER ECCOTHANE 7510
84457	1,281	RUBBER ECCOTHANE CPC18
84458	1,281	RUBBER ECCOTHANE CPC19
84459	1,282	RUBBER ECCOTHANE CPC39
84460	1,282	RUBBER ECCOTHANE CPC41
84461	1,122	PLASTIC STYCAST 1269A
84462	1,122	PLASTIC STYCAST 1495
84463	1,122	PLASTIC STYCAST 2057
84464	1,122	PLASTIC STYCAST 2058
84465	1,122	PLASTIC STYCAST 2651-1
84466	1,122	PLASTIC STYCAST 2651-40
84467	1,123	PLASTIC STYCAST 2651MM-1
84468	1,123	PLASTIC STYCAST 2750FR-N
84469	1,123	PLASTIC STYCAST 2760
84470	1,123	PLASTIC STYCAST 2850MT
84471	1,123	PLASTIC STYCAST 2851FT
84472	1,123	PLASTIC STYCAST 2851KT
84473	1,123	PLASTIC STYCAST 2851MT
84474	1,123	PLASTIC STYCAST 3020SC
84475	1,123	PLASTIC STYCAST 3180M
84476	1,018	PLASTIC NYLON 1003-6
84477	1,018	PLASTIC NYLON 1100
84478	1,018	PLASTIC NYLON 1200
84479	1,018	PLASTIC NYLON 1300
84480	1,018	PLASTIC NYLON 1310
84481	1,018	PLASTIC NYLON 1310-1
84482	1,019	PLASTIC NYLON 1310-4
84483	1,019	PLASTIC NYLON 1310-2
84484	1,019	PLASTIC NYLON 1310-6
84485	1,019	PLASTIC NYLON 1400
84486	1,019	PLASTIC NYLON 1400-1
84487	1,019	PLASTIC NYLON 1403-1
84488	1,019	PLASTIC NYLON 1403-2
84489	1,019	PLASTIC NYLON 1500
84490	1,019	PLASTIC NYLON 1500-1
84491	1,105	PLASTIC RP-4036/RP-1500H
84492	1,019	PLASTIC NYLON 1500-2
84493	1,019	PLASTIC NYLON 1503-1
84494	1,105	PLASTIC RP-4104R/1500H
84495	1,019	PLASTIC NYLON 1503-2
84496	1,134	PLASTIC TDT-177-15
84497	1,019	PLASTIC NYLON 1600
84498	1,020	PLASTIC NYLON 1600-1
84499	1,134	PLASTIC TDT-177-62
84500	1,020	PLASTIC NYLON 1600-2
84501	1,021	PLASTIC NYLON 7010
84502	1,021	PLASTIC NYLON 7013
84503	1,021	PLASTIC NYLON 7020
84504	1,021	PLASTIC NYLON 7023
84505	1,021	PLASTIC NYLON 7030
84506	1,022	PLASTIC NYLON 7033
84507	36	ADHESIVE ARALDITE 1138/HY906/DY062
84508	37	ADHESIVE ARALDITE 6010/AROMATIC DIAMINE
84509	1,018	PLASTIC NYLON 1003-2
84510	37	ADHESIVE ARALDITE 6010/DICY
84511	1,018	PLASTIC NYLON 1003-1
84512	37	ADHESIVE ARALDITE 6010/HY940/EHT939
84513	1,018	PLASTIC NYLON 1003
84514	37	ADHESIVE ARALDITE 6010/POLYAMIDE
84515	37	ADHESIVE ARALDITE 6010/TETA
84516	1,018	PLASTIC NYLON 1000-6
84517	38	ADHESIVE ARALDITE 7071/DICY
84518	1,018	PLASTIC NYLON 1000-4

MSFC-HDBK-527 REV F 9999942 0006821 2

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
84519	1,017	PLASTIC NYLON 1000-2
84520	38	ADHESIVE ARALDITE 7071/POLYAMIDE
84521	1,017	PLASTIC NYLON 1000-1
84522	1,017	PLASTIC NYLON 1000
84523	1,019	PLASTIC NYLON 1400-2
84524	38	ADHESIVE ARALDITE EPN1138/BR3MEA
84525	64	ADHESIVE CASTALL U2003
84526	38	ADHESIVE ARALDITE EPN1138/HT972
84527	38	ADHESIVE ARALDITE EPN1138/HY907/DY062
84528	64	ADHESIVE CASTALL U2004
84529	64	ADHESIVE CASTALL U2007
84530	39	ADHESIVE ARALDITE MY720/HY906/FORM VAR 7/70
84531	100	ADHESIVE EA901NA/B1
84532	1,122	PLASTIC STYCAST 1267
84533	833	PLASTIC C60 STD
84534	833	PLASTIC C61 STD
84535	833	PLASTIC C9-4183/HD3485
84536	833	PLASTIC C9-4186/HD3485
84537	862	PLASTIC DK17-01
84538	862	PLASTIC DK18-05
84539	862	PLASTIC DK27
84540	862	PLASTIC DK28
84541	863	PLASTIC DK30
84542	863	PLASTIC DK32
84543	862	PLASTIC DK17
84544	862	PLASTIC DK17-05
84545	877	PLASTIC EE0036/HD3561
84546	877	PLASTIC EE0036/HD3615
84547	877	PLASTIC EE0067/HD3404
84548	877	PLASTIC EE0067/HD3561
84549	878	PLASTIC EE0067/HD3615
84550	878	PLASTIC EE0149/HD3561
84551	878	PLASTIC EE1067/HD3561
84552	878	PLASTIC EE1068/HD0242
84553	878	PLASTIC EE1068/HD0243
84554	878	PLASTIC EE1087/HD3404
84555	878	PLASTIC EE1087/HD3561
84556	878	PLASTIC EE1087/HD3615
84557	878	PLASTIC EE4143/HD3404
84558	878	PLASTIC EE4143/HD3475 FILLED
84559	878	PLASTIC EE4143/HD3490
84560	878	PLASTIC EE4183/HD0242
84561	878	PLASTIC EE4183/HD0243
84562	878	PLASTIC EE4183/HD3404
84563	879	PLASTIC EE4183/HD3410
84564	879	PLASTIC EE4183/HD3469
84565	879	PLASTIC EE4183/HD3475 FILLED
84566	879	PLASTIC EE4183/HD3485
84567	879	PLASTIC EE4183/HD3490
84568	879	PLASTIC EE4183/HD3537
84569	879	PLASTIC EE4183/HD3561
84570	879	PLASTIC EE4183/HD3615
84571	879	PLASTIC EE4183/HD3719
84572	879	PLASTIC EE4183/HD3840
84573	879	PLASTIC EE4186/HD3537
84574	879	PLASTIC EE4799/HD3596
84575	889	PLASTIC EO0102
84576	889	PLASTIC EO0103
84577	889	PLASTIC EO0104
84578	889	PLASTIC EO0105
84579	65	ADHESIVE CASTALL U2009
84580	890	PLASTIC EO0106
84581	65	ADHESIVE CASTALL U2010
84582	65	ADHESIVE CASTALL U2012
84583	65	ADHESIVE CASTALL U2015
84584	890	PLASTIC EO0107
84585	65	ADHESIVE CASTALL U2018
84586	890	PLASTIC EO0108
84587	65	ADHESIVE CASTALL U2019
84588	890	PLASTIC EO0109
84589	65	ADHESIVE CASTALL U2020
84590	890	PLASTIC EO0110
84591	890	PLASTIC EO1016
84592	65	ADHESIVE CASTALL U2020FR
84593	890	PLASTIC EO1035
84594	890	PLASTIC EO1038
84595	65	ADHESIVE CASTALL U2024
84596	899	PLASTIC ES4412
84597	65	ADHESIVE CASTALL U2028
84598	898	PLASTIC ES0002
84599	898	PLASTIC ES0007
84600	898	PLASTIC ES0032
84601	65	ADHESIVE CASTALL U2036
84602	66	ADHESIVE CASTALL U2040
84603	66	ADHESIVE CASTALL U2048
84604	898	PLASTIC ES0033
84605	66	ADHESIVE CASTALL U2052
84606	898	PLASTIC ES0042
84607	898	PLASTIC ES0043
84608	898	PLASTIC ES0047
84609	899	PLASTIC ES0052
84610	899	PLASTIC ES0269
84611	899	PLASTIC ES0329
84612	899	PLASTIC ES4212
84613	899	PLASTIC ES4312
84614	899	PLASTIC ES4322
84615	899	PLASTIC ES4323
84616	899	PLASTIC ES4325
84617	899	PLASTIC ES4326
84619	988	PLASTIC MG15F
84620	988	PLASTIC MG18
84621	988	PLASTIC MG25F
84622	988	PLASTIC MG25F-LMP
84623	988	PLASTIC MG25F-LMP(F)
84624	988	PLASTIC MG25F-LMP-1
84625	988	PLASTIC MG35F
84626	979	PLASTIC LUSTRAN ABS911
84627	988	PLASTIC MG35F-01
84628	979	PLASTIC LUSTRAN ABS914HM
84629	988	PLASTIC MG6-0260

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
84630	979	PLASTIC LUSTRAN ABS921UV
84631	988	PLASTIC MG8F-0134
84632	989	PLASTIC MH19F-0217
84633	989	PLASTIC MH19F-0294
84634	979	PLASTIC LUSTRAN ABSPG298 PLATED
84635	989	PLASTIC MH2-W254
84636	989	PLASTIC MH6-W588
84637	979	PLASTIC LUSTRAN ABSPG298 UNPLATED
84638	989	PLASTIC MH9-02 BLACK
84639	979	PLASTIC LUSTRAN ELITE LGM
84640	1,095	PLASTIC RE2039/HD3404
84641	979	PLASTIC LUSTRAN ULTRA HX
84642	1,095	PLASTIC RE2038/HD3404
84643	1,095	PLASTIC RE2038/HD3475 UNFILLED
84644	979	PLASTIC LUSTRAN ULTRA MX
84645	39	ADHESIVE ARALDITE MY720/HY972/FORM VAR 7/70
84646	1,095	PLASTIC RE2038/HD3490
84647	1,095	PLASTIC RE2039/HD242
84648	1,095	PLASTIC RE2039/HD0243
84649	841	PLASTIC CG1310R/RP1520H
84650	1,189	PLASTIC TRIAZ 1120
84651	1,095	PLASTIC RE2039/HD3410
84652	841	PLASTIC CGL1310R/RP1520H
84653	1,095	PLASTIC RE2039/HD3469
84654	1,189	PLASTIC TRIAZ 1125
84655	841	PLASTIC CGL1320R/RP1500H
84656	1,096	PLASTIC RE2039/HD3475 UNFILLED
84657	1,096	PLASTIC RER2039/HD3490
84658	116	ADHESIVE ECN1235/906/MBDMA
84659	1,228	PLASTIC VYDYNE 21
84661	1,096	PLASTIC RE2039/HD3561
84662	1,228	PLASTIC VYDYNE 21SP
84663	1,096	PLASTIC RE2039/HD3615
84664	1,228	PLASTIC VYDYNE 21X
84665	1,096	PLASTIC RE2039/HD3719
84666	1,228	PLASTIC VYDYNE 22H
84667	1,096	PLASTIC RE2039/HD3840
84668	1,228	PLASTIC VYDYNE 22HSP
84669	1,368	RUBBER US0059
84670	1,368	RUBBER US0066
84671	1,368	RUBBER US0075
84672	1,228	PLASTIC VYDYNE 24NSP
84673	1,368	RUBBER US0081
84674	1,368	RUBBER US0082
84675	1,228	PLASTIC VYDYNE 25W
84676	1,368	RUBBER US0083
84677	1,228	PLASTIC VYDYNE 60H
84678	1,368	RUBBER US0084
84679	1,228	PLASTIC VYDYNE 65B
84680	1,269	RUBBER ABRASHUN 5015
84681	1,269	RUBBER ABRASHUN 5035
84682	1,228	PLASTIC VYDYNE 66B
84683	1,269	RUBBER ABRASHUN 5040
84684	1,228	PLASTIC VYDYNE 909
84685	1,270	RUBBER ABRASHUN 5045
84686	1,228	PLASTIC VYDYNE M340
84687	1,270	RUBBER ABRASHUN 5055
84688	1,270	RUBBER ABRASHUN 5065
84689	1,270	RUBBER ABRASHUN 5075
84690	841	PLASTIC CGL1320R/RP1520H
84691	1,229	PLASTIC VYDYNE M344
84692	1,270	RUBBER ABRASHUN 5088
84693	1,229	PLASTIC VYDYNE M345
84694	1,270	RUBBER ABRASHUN 5095
84695	1,270	RUBBER ABRASHUN 5097
84696	1,229	PLASTIC VYDYNE R-100
84697	1,229	PLASTIC VYDYNE R-200
84698	1,270	RUBBER ABRASHUN 5098
84699	1,229	PLASTIC VYDYNE R-220
84700	116	ADHESIVE ECN1235/907/066
84701	1,229	PLASTIC VYDYNE R-250
84702	116	ADHESIVE ECN1235/BF3MEA
84703	864	PLASTIC DOLFLEX CC1015
84704	116	ADHESIVE ECN1273/906/MBDMA
84705		DELETED SEE 05218
84706	864	PLASTIC DOLPHON CB1076
84707	116	ADHESIVE ECN1299/906
84708	1,229	PLASTIC VYDYNE R-400
84709	864	PLASTIC DOLPHON CB1078
84710	1,229	PLASTIC VYDYNE R-513
84711	864	PLASTIC DOLPHON CB1078/RE2000
84712	1,229	PLASTIC VYDYNE R-513H
84713	1,229	PLASTIC VYDYNE R-533
84714	864	PLASTIC DOLPHON CB1078/RE2001
84715	864	PLASTIC DOLPHON CB1078/RE2005
84716	864	PLASTIC DOLPHON CB1078/RE2009
84717	864	PLASTIC DOLPHON CB1078/RE2010
84718	1,361	RUBBER SILICONE SI600
84719	864	PLASTIC DOLPHON CB1078/RE2019
84720	1,361	RUBBER SILICONE SI700
84721	864	PLASTIC DOLPHON CB1112A/RE2000
84722	864	PLASTIC DOLPHON CB1112A/CB1112B
84723	864	PLASTIC DOLPHON CB1116
84724	865	PLASTIC DOLPHON CC1079/RE2000
84725	865	PLASTIC DOLPHON CC1079/RE2005
84726	865	PLASTIC DOLPHON CC1095
84727	865	PLASTIC DOLPHON CC1106
84728	95	ADHESIVE DOLPHON CN1119
84729	865	PLASTIC DOLPHON CR1035
84730	865	PLASTIC DOLPHON CR1050
84731	1,229	PLASTIC VYDYNE R-533H
84732	1,229	PLASTIC VYDYNE R-538H-02
84733	1,229	PLASTIC VYDYNE R-543
84734	1,229	PLASTIC VYDYNE R-543H
84735	950	PLASTIC KOSTIL AF1/PA
84736	951	PLASTIC KOSTIL AF3/PA
84737	951	PLASTIC KOSTIL AFL1/PA
84738	951	PLASTIC KOSTIL BF/PA
84739	1,035	PLASTIC PETROTHENE LB 603
84740	1,035	PLASTIC PETROTHENE LB 851

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006823 6

MATCD	PAGE	DESIGNATION
84741	92	ADHESIVE DOLCHEM 3400
84742	1,035	PLASTIC PETROTHENE LB 861
84743	92	ADHESIVE DOLCHEM 3420
84744	1,036	PLASTIC PETROTHENE LS 404
84745	92	ADHESIVE DOLCHEM 6002
84746	1,036	PLASTIC PETROTHENE LS 506
84747	1,036	PLASTIC PETROTHENE LS 509
84748	92	ADHESIVE DOLCHEM 6016
84749	1,036	PLASTIC PETROTHENE LS 511
84750	92	ADHESIVE DOLCHEM 6040
84751	92	ADHESIVE DOLCHEM 60466
84752	92	ADHESIVE DOLCHEM 6060
84753	93	ADHESIVE DOLCHEM 6065
84754	93	ADHESIVE DOLCHEM 6068
84755	93	ADHESIVE DOLCHEM 6109
84756	835	PLASTIC CALIBRE 200-10
84757	835	PLASTIC CALIBRE 200-15
84758	835	PLASTIC CALIBRE 200-22
84759	835	PLASTIC CALIBRE 200-4
84760	835	PLASTIC CALIBRE 200-6
84761	1,189	PLASTIC TPR5680
84762	835	PLASTIC CALIBRE 2060-10
84763	835	PLASTIC CALIBRE 2060-15
84764	835	PLASTIC CALIBRE 2060-22
84765	835	PLASTIC CALIBRE 2060-4
84766	835	PLASTIC CALIBRE 2060-6
84767	835	PLASTIC CALIBRE 2080-15
84768	836	PLASTIC CALIBRE 2080-4
84769	836	PLASTIC CALIBRE 300-10
84770	836	PLASTIC CALIBRE 300-15
84771	836	PLASTIC CALIBRE 300-22
84772	836	PLASTIC CALIBRE 300-4
84773	1,036	PLASTIC PETROTHENE LS 514
84774	836	PLASTIC CALIBRE 300-6
84775	1,036	PLASTIC PETROTHENE LS 523
84776	836	PLASTIC CALIBRE 510
84777	1,036	PLASTIC PETROTHENE LS 525
84778	836	PLASTIC CALIBRE 550
84779	1,037	PLASTIC PETROTHENE LS 528
84780	836	PLASTIC CALIBRE 700-10
84781	1,037	PLASTIC PETROTHENE LS 530
84782	836	PLASTIC CALIBRE 700-15
84783	836	PLASTIC CALIBRE 700-6
84784	836	PLASTIC CALIBRE 800-10
84785	1,037	PLASTIC PETROTHENE LS 545
84786	1,037	PLASTIC PETROTHENE LS 556
84787	836	PLASTIC CALIBRE 800-15
84788	1,037	PLASTIC PETROTHENE LS 606
84789	836	PLASTIC CALIBRE 800-6
84790	1,037	PLASTIC PETROTHENE LS 609
84791	934	PLASTIC HDPE 25053P
84792	934	PLASTIC HDPE 25050P
84793	1,037	PLASTIC PETROTHENE LS 618
84794	934	PLASTIC HDPE 69065P
84795	1,037	PLASTIC PETROTHENE LS 630
84796	1,116	PLASTIC SAN 125
84797	1,369	RUBBER VITON 1097
84798	1,037	PLASTIC PETROTHENE LS 901
84799	1,093	PLASTIC PULSE ENGINEERING RESINS 600
84800	1,037	PLASTIC PETROTHENE LY 656
84801	1,093	PLASTIC PULSE ENGINEERING RSINS 700
84802	1,037	PLASTIC PETROTHENE NA 117
84803	1,093	PLASTIC PULSE ENGINEERING RESINS 710
84804	1,037	PLASTIC PETROTHENE NA 202
84805	1,093	PLASTIC PULSE ENGINEERING RESINS 830
84806	1,037	PLASTIC PETROTHENE NA 208
84807	1,093	PLASTIC PULSE ENGINEERING RESINS 855
84808	1,037	PLASTIC PETROTHENE NA 213
84809	1,093	PLASTIC PULSE ENGINEERING RESINS 869
84810	1,130	PLASTIC STYRON 656D
84811	1,130	PLASTIC STYRON 666D
84812	1,130	PLASTIC STYRON 678D
84813	1,131	PLASTIC STYRON 678U
84814	1,131	PLASTIC STYRON 685
84815	1,038	PLASTIC PETROTHENE NA 225
84816	1,131	PLASTIC STYRON 685D
84817	1,038	PLASTIC PETROTHENE NA 226
84818	1,131	PLASTIC STYRON 697
84819	1,189	PLASTIC TYRIL 1000
84820	1,038	PLASTIC PETROTHENE NA 241
84821	1,038	PLASTIC PETROTHENE NA 246
84822	862	PLASTIC DIXON 20% GLASS 5% GRAPHITE
84823	1,038	PLASTIC PETROTHENE NA 249
84824	862	PLASTIC DIXON 55% BRONZE 5% MOS2
84825	1,038	PLASTIC PETROTHENE NA 254
84826	862	PLASTIC DIXON 60% BRONZE
84827	862	PLASTIC DIXON NYLON 6/6 40% CF
84828	1,038	PLASTIC PETROTHENE NA 270
84829	1,189	PLASTIC TYRIL 1000B
84830	1,189	PLASTIC TYRIL 1020
84831	1,038	PLASTIC PETROTHENE NA 295
84832	1,189	PLASTIC TYRIL 1021
84833	1,189	PLASTIC TYRIL 1031
84834	1,189	PLASTIC TYRIL 880
84835	1,189	PLASTIC TYRIL 880B
84836	858	PLASTIC DERAKANE 411-45
84837	1,199	PLASTIC ULTRATHENE UE 631 19% VA
84838	859	PLASTIC DERAKANE 470-36
84839	859	PLASTIC DERAKANE 510A-40
84840	859	PLASTIC DERAKANE 530
84841	1,199	PLASTIC ULTRATHENE UE 633 19% VA
84842	859	PLASTIC DERAKANE 8084
84843	1,199	PLASTIC ULTRATHENE UE 635 9% VA
84844	980	PLASTIC MAGNUM ABS213 RESIN
84845	1,199	PLASTIC ULTRATHENE UE 637 9% VA
84846	980	PLASTIC MAGNUM ABS341 RESIN
84847	1,199	PLASTIC ULTRATHENE UE 655 9% VA
84848	980	PLASTIC MAGNUM ABS343 RESIN
84849	980	PLASTIC MAGNUM ABS4500UV RESIN
84850	980	PLASTIC MAGNUM ABS545 RESIN

MATCD	PAGE	DESIGNATION
84851	981	PLASTIC MAGNUM ABS9010 RESIN
84852	981	PLASTIC MAGNUM ABS9020 RESIN
84853	1,199	PLASTIC ULTRATHENE UE 657 12% VA
84854	981	PLASTIC MAGNUM ABS9030 RESIN
84855	981	PLASTIC MAGNUM ABS9408 RESIN
84856	981	PLASTIC MAGNUM ABS941 RESIN
84857	1,368	RUBBER VESTAMID E40-S3
84858	981	PLASTIC MAGNUM ABS9450P RESIN
84859	1,369	RUBBER VESTAMID E50-C5-S2
84860	981	PLASTIC MAGNUM ABS95CLR RESIN
84861	981	PLASTIC MAGNUM ABSFG960 RESIN
84862	1,369	RUBBER VESTAMID E47-S3
84863	1,309	RUBBER PELLETHANE 2102-75A
84864	1,369	RUBBER VESTAMID E55-S3
84865	1,309	RUBBER PELLETHANE 2102-80A
84866	1,369	RUBBER VESTAMID E57-C5-S2
84867	1,309	RUBBER PELLETHANE 2102-80AE
84868	1,309	RUBBER PELLETHANE 2102-80PF
84869	1,309	RUBBER PELLETHANE 2102-85A
84870	1,369	RUBBER VESTAMID E62-S3
84871	1,274	RUBBER CALTHANE 1400
84872	1,309	RUBBER PELLETHANE 2102-90A
84873	1,369	RUBBER VESTAMID E67-C5-S2
84874	1,310	RUBBER PELLETHANE 2102-90AE
84875	1,274	RUBBER CALTHANE 1700
84876	1,224	PLASTIC VESTODUR 1000
84877	1,310	RUBBER PELLETHANE 2102-90AR
84878	1,310	RUBBER PELLETHANE 2102-90PF
84879	1,224	PLASTIC VESTODUR 2000
84880	1,310	RUBBER PELLETHANE 2103-70A
84881	1,224	PLASTIC VESTODUR 2000 SO
84882	1,274	RUBBER CALTHANE 1900
84883	1,310	RUBBER PELLETHANE 2103-80A
84884	1,224	PLASTIC VESTODUR 3000
84885	1,310	RUBBER PELLETHANE 2103-80AE
84886	1,310	RUBBER PELLETHANE 2103-80AEF
84887	1,224	PLASTIC VESTODUR GK 30
84888	1,310	RUBBER PELLETHANE 2103-80AES
84889	1,225	PLASTIC VESTODUR MGF 30
84890	1,274	RUBBER CALTHANE ND1100
84891	1,310	RUBBER PELLETHANE 2103-80PF
84892	1,274	RUBBER CALTHANE ND2300
84893	1,225	PLASTIC VESTODUR MIN 125
84894	1,310	RUBBER PELLETHANE 2103-80WC
84895	1,225	PLASTIC VESTODUR SGF 15
84896	1,311	RUBBER PELLETHANE 2130-85ACR
84897	1,274	RUBBER CALTHANE ND3200
84898	1,310	RUBBER PELLETHANE 2103-85AE
84899	1,225	PLASTIC VESTODUR SGF 20
84900	1,310	RUBBER PELLETHANE 2103-90A
84901	1,274	RUBBER CALTHANE NF1200
84902	1,225	PLASTIC VESTODUR SGF 20 SO
84903	1,310	RUBBER PELLETHANE 2103-90ACR
84904	1,225	PLASTIC VESTODUR SGF 30
84905	1,274	RUBBER CALTHANE NF1300
84906	1,310	RUBBER PELLETHANE 2103-90AE
84907	1,225	PLASTIC VESTODUR SGF 30 SO
84908	1,309	RUBBER PELLETHANE 2013-90AEF
84909	1,274	RUBBER CALTHANE NF1300-60A
84910	1,311	RUBBER PELLETHANE 2202-93A
84911	1,311	RUBBER PELLETHANE 2351-85AE
84912	1,274	RUBBER CALTHANE NF1500
84913	1,225	PLASTIC VESTODUR SGF 50
84914	1,274	RUBBER CALTHANE NF2300
84915	1,311	RUBBER PELLETHANE 2352-70A
84916	1,311	RUBBER PELLETHANE 2355-75A
84917	1,274	RUBBER CALTHANE NF310W
84918	1,311	RUBBER PELLETHANE 2355-80A
84919	1,311	RUBBER PELLETHANE 2355-80AE
84920	1,311	RUBBER PELLETHANE 2355-80AEF
84921	852	PLASTIC CR39
84922	1,311	RUBBER PELLETHANE 2355-85ABR
84923	1,311	RUBBER PELLETHANE 2355-90A
84924	936	PLASTIC HIRI 2 CASTING RESIN (EXTRA)
84925	1,311	RUBBER PELLETHANE 2355-90AE
84926	1,311	RUBBER PELLETHANE 2355-95ACR
84927	1,311	RUBBER PELLETHANE 2355-95AE
84928	1,311	RUBBER PELLETHANE 2355-95AEF
84929	64	ADHESIVE CASTALL S1277
84930	1,312	RUBBER PELLETHANE 2355-95AESP
84931	64	ADHESIVE CASTALL U2001
84932	1,312	RUBBER PELLETHANE 2363-75A
84933	936	PLASTIC HIRI 2 CASTING RESIN (NON-FLAMMABLE)
84934	1,312	RUBBER PELLETHANE 2363-80A
84935	64	ADHESIVE CASTALL U2002
84936	1,312	RUBBER PELLETHANE 2363-80AE
84937	1,312	RUBBER PELLETHANE 2363-90A
84938	951	PLASTIC KYNAR 461
84939	1,312	RUBBER PELLETHANE 2363-90AE
84940	952	PLASTIC KYNAR 721
84941	796	PLASTIC 1-5021
84942	5	ADHESIVE 1890
84943		DELETED SEE 60384
84944	1,101	PLASTIC RIMPLAST PTEE 601
84945	1,269	RUBBER 3-6550
84947	1,101	PLASTIC RIMPLAST PTEE 602
84948	801	PLASTIC 307
84949	952	PLASTIC KYNAR 723
84950	1,101	PLASTIC RIMPLAST PTSEBS 1204
84951	801	PLASTIC 308
84952	952	PLASTIC KYNAR 741
84953	1,101	PLASTIC RIMPLAST PTSEBS 2204
84954	9	ADHESIVE 4-2805
84955	951	PLASTIC KYNAR 710
84956	9	ADHESIVE 4-2817
84957	1,101	PLASTIC RIMPLAST PTUA 102
84958	952	PLASTIC KYNAR 720
84959	803	PLASTIC 480
84960	952	PLASTIC KYNAR 730
84961	1,101	PLASTIC RIMPLAST PTUA 103

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006825 T ■

MATCD	PAGE	DESIGNATION
84962	85	ADHESIVE DC6-1125
84963	952	PLASTIC KYNAR 736
84964	1,101	PLASTIC RIMPLAST PTUE 101
84965	806	PLASTIC 631
84966	210	ADHESIVE PERMALOK HH190
84967	1,101	PLASTIC RIMPLAST PTUE 102
84968	85	ADHESIVE DC 92-009
84969	1,101	PLASTIC RIMPLAST PTUE 202
84970	211	ADHESIVE PERMALOK MM115
84971	85	ADHESIVE DC92-010 RUBBER SILICONE
84972	1,101	PLASTIC RIMPLAST PTUE 203
84973	211	ADHESIVE PERMALOK PAS10
84974	85	ADHESIVE DC93-006
84975	209	ADHESIVE PERMABOND 107
84976	1,101	PLASTIC RIMPLAST PTUE 205
84977	85	ADHESIVE DC93-118
84978	209	ADHESIVE PERMABOND 108
84979	209	ADHESIVE PERMABOND 268
84980	86	ADHESIVE DC94-011
84981	210	ADHESIVE PERMABOND 747
84982	86	ADHESIVE DC94-031
84983	210	ADHESIVE PERMABOND ESP108
84984	86	ADHESIVE DC96-082 RUBBER SILICONE
84985	210	ADHESIVE PERMABOND ESP109
84986	1,102	PLASTIC RIMPLAST PTUE 302
84987	1,094	PLASTIC Q1-5036
84988	210	ADHESIVE PERMABOND ESP110
84989	1,102	PLASTIC RIMPLAST PTUE 332
84990	1,317	RUBBER S5370
84991	1,318	RUBBER SILASTIC 1890
84992	1,102	PLASTIC RIMPLAST R1000
84993	210	ADHESIVE PERMALOK HH194
84994	1,318	RUBBER SILASTIC 437 BASE
84995	210	ADHESIVE PERMALOK HH195
84996	1,318	RUBBER SILASTIC 55U/75U
84997	1,318	RUBBER SILASTIC 590
84998	226	ADHESIVE QUICKBOND 614/610
84999	1,318	RUBBER SILASTIC 591
85000	1,318	RUBBER SILASTIC 595
85001	1,100	PLASTIC RIMPLAST NYLON 12
85002	1,318	RUBBER SILASTIC 596
85003	1,318	RUBBER SILASTIC 598
85004	1,100	PLASTIC RIMPLAST NYLON 6/6
85005	1,318	RUBBER SILASTIC 599
85006	1,100	PLASTIC RIMPLAST PTA 1201
85007	1,318	RUBBER SILASTIC 745U
85008	1,100	PLASTIC RIMPLAST PTA 1202
85009	1,319	RUBBER SILASTIC 746U
85010	1,101	PLASTIC RIMPLAST PTA 6601
85011	1,319	RUBBER SILASTIC 747U
85012	1,102	PLASTIC RIMPLAST R5000
85013	1,101	PLASTIC RIMPLAST PTA 6602
85014	1,101	PLASTIC RIMPLAST PTA 6631
85015	1,102	PLASTIC RIMPLAST RF-1006
85016	1,319	RUBBER SILASTIC 75U
85017	1,102	PLASTIC RIMPLAST RF-5006
85018	1,102	PLASTIC RIMPLAST RL-4610
85019	1,319	RUBBER SILASTIC 75U/8PPH CAB-O-SIL MS7/DMBPH
85020	1,102	PLASTIC RIMPLAST RL-4620
85021	982	PLASTIC MARLEX 5502
85022	983	PLASTIC MARLEX 6003
85023	1,320	RUBBER SILASTIC FORMULA A
85024	1,320	RUBBER SILASTIC FORMULA B
85025	1,320	RUBBER SILASTIC FORMULA C
85026	983	PLASTIC MARLEX 6007
85027	1,320	RUBBER SILASTIC FORMULA D
85028	983	PLASTIC MARLEX BMN 55500
85029	1,320	RUBBER SILASTIC GP437
85030	1,321	RUBBER SILASTIC GP45
85031	1,321	RUBBER SILASTIC GP70
85032	1,321	RUBBER SILASTIC HS
85033	1,321	RUBBER SILASTIC HS30
85034	1,321	RUBBER SILASTIC HS30/HS50
85035	1,321	RUBBER SILASTIC HS50
85036	1,321	RUBBER SILASTIC HS50/HS70
85037	1,321	RUBBER SILASTIC HS70
85038	1,321	RUBBER SILASTIC J
85039	1,321	RUBBER SILASTIC L
85040	1,321	RUBBER SILASTIC LCS740
85041	1,321	RUBBER SILASTIC LS2249U
85042	1,321	RUBBER SILASTIC LS2311U
85043	1,321	RUBBER SILASTIC LS2380U
85044	1,322	RUBBER SILASTIC LS2840
85045	1,322	RUBBER SILASTIC LS2860
85046	1,322	RUBBER SILASTIC LS53U
85047	1,322	RUBBER SILASTIC LS63U
85048	1,322	RUBBER SILASTIC LT50
85049	983	PLASTIC MARLEX BMN TR880
85050	1,322	RUBBER SILASTIC NPC40
85051	983	PLASTIC MARLEX CL100
85052	1,322	RUBBER SILASTIC NPC40/NPC80
85053	1,323	RUBBER SILASTIC NPC80
85054	1,365	RUBBER SYLGARD 527
85055	1,365	RUBBER SYLGARD 567
85056	1,365	RUBBER SYLGARD 577
85057	936	PLASTIC HIMOD N66GL40
85058	817	PLASTIC ALATHON 20
85059	817	PLASTIC ALATHON 20-6064
85060	817	PLASTIC ALATHON 2005
85061	817	PLASTIC ALATHON 2010
85062	817	PLASTIC ALATHON 2020
85063	817	PLASTIC ALATHON 2020T
85064	191	ADHESIVE MARK 231 EPOXY PUTTY
85065	885	PLASTIC ELVAMIDE 8023
85066	885	PLASTIC ELVAMIDE 8061
85067	983	PLASTIC MARLEX EHM 6001
85068	886	PLASTIC ELVAMIDE 8061M
85069	983	PLASTIC MARLEX CL50
85070	886	PLASTIC ELVAMIDE 8062S
85071	886	PLASTIC ELVAMIDE 8063

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006826 1

MATCD	PAGE	DESIGNATION
85072	886	PLASTIC ELVAMIDE 8064
85073	886	PLASTIC ELVAMIDE 8066
85074	983	PLASTIC MARLEX EHM 6006
85075	886	PLASTIC ELVAX 150
85076	192	ADHESIVE MARK 8
85077	886	PLASTIC ELVAX 240
85078	1,053	PLASTIC POLIFIL T-40
85079	886	PLASTIC ELVAX 250
85080	983	PLASTIC MARLEX EMN TR885
85081	886	PLASTIC ELVAX 260
85082	886	PLASTIC ELVAX 265
85083	886	PLASTIC ELVAX 350
85084	1,053	PLASTIC POLIFIL T-20
85085	886	PLASTIC ELVAX 360
85086	886	PLASTIC ELVAX 40W
85087	1,052	PLASTIC POLIFIL RMT-40
85088	983	PLASTIC MARLEX ER9-0002
85089	886	PLASTIC ELVAX 450
85090	1,052	PLASTIC POLIFIL RMT-20
85091	887	PLASTIC ELVAX 46
85092	887	PLASTIC ELVAX 460
85093	1,052	PLASTIC POLIFIL RMC-40
85094	887	PLASTIC ELVAX 46L
85095	983	PLASTIC MARLEX ER9-0020
85096	1,052	PLASTIC POLIFIL RMC-20
85097	887	PLASTIC ELVAX 470
85098	1,052	PLASTIC POLIFIL M40
85099	887	PLASTIC ELVAX 550
85100	983	PLASTIC MARLEX HHM 4515
85101	1,052	PLASTIC POLIFIL M20
85102	887	PLASTIC ELVAX 560
85103	983	PLASTIC MARLEX HHM 4903
85104	1,052	PLASTIC POLIFIL HM40
85105	887	PLASTIC ELVAX 565
85106	1,052	PLASTIC POLIFIL HM20
85107	983	PLASTIC MARLEX HHM 5202
85108	887	PLASTIC ELVAX 650
85109	1,052	PLASTIC POLIFIL CAS-40
85110	984	PLASTIC MARLEX HHM TR210
85111	887	PLASTIC ELVAX 660
85112	1,052	PLASTIC POLIFIL C-40
85113	887	PLASTIC ELVAX 670
85114	984	PLASTIC MARLEX HHM TR226
85115	1,052	PLASTIC POLIFIL C-20
85116	887	PLASTIC ELVAX 750
85117	984	PLASTIC MARLEX HHM TR230
85118	887	PLASTIC ELVAX 760
85119	984	PLASTIC MARLEX HHM TR232
85120	887	PLASTIC ELVAX 770
85121	984	PLASTIC MARLEX HHM TR250
85122	887	PLASTIC ELVAX LDPE
85123	984	PLASTIC MARLEX HHM TR416
85124	931	PLASTIC GRZ 70G13 HS1L
85125	931	PLASTIC GRZ 70G33 HS1L
85126	984	PLASTIC MARLEX HMN 4550
85127	931	PLASTIC GRZ 70G43L
85128	984	PLASTIC MARLEX HMN 5060
85129	1,049	PLASTIC PLENCO 07500
85130	949	PLASTIC KELDAX 6826Q
85131	949	PLASTIC KELDAX 8208
85132	1,049	PLASTIC PLENCO 07502
85133	984	PLASTIC MARLEX HMN 54140
85134	949	PLASTIC KELDAX 8208Q
85135	1,050	PLASTIC PLENCO 07507
85136	984	PLASTIC MARLEX HMN 5580
85137	949	PLASTIC KELDAX 9103
85138	1,050	PLASTIC PLENCO 07523
85139	1,050	PLASTIC PLENCO 07552
85140	949	PLASTIC KELDAX 9105
85141	949	PLASTIC KELDAX 9106
85142	1,050	PLASTIC PLENCO 07579
85143	984	PLASTIC MARLEX HMN 6060
85144	996	PLASTIC MINLON 22C
85145	1,050	PLASTIC PLENCO CELLULOSE-FILLED ALKYD
85146	984	PLASTIC MARLEX HMN TR938
85147	996	PLASTIC MINLON 91C
85148	996	PLASTIC MINLON FR60
85149	984	PLASTIC MARLEX HMN TR942
85150	1,050	PLASTIC PLENCO COPOLYMER ELECTRICAL
85151	1,008	PLASTIC NUCREL 010
85152	1,008	PLASTIC NUCREL 035
85153	985	PLASTIC MARLEX HMN TR950
85154	1,008	PLASTIC NUCREL 403
85155	1,050	PLASTIC PLENCO ELECTRICAL AND ELECTRONIC ALKYD
85156	1,008	PLASTIC NUCREL 410
85157	1,009	PLASTIC NUCREL 535
85158	985	PLASTIC MARLEX HMN TR954
85159	1,009	PLASTIC NUCREL 599
85160	1,050	PLASTIC PLENCO ELECTRICAL MOLDING COMPOUND
85161	1,009	PLASTIC NUCREL 699
85162	1,009	PLASTIC NUCREL 714
85163	1,050	PLASTIC PLENCO GENERAL PURPOSE ALKYD
85164	1,009	PLASTIC NUCREL 925
85165	1,047	PLASTIC PLENCO 04400
85166	1,009	PLASTIC NUCREL 960
85167	1,047	PLASTIC PLENCO 04414
85168	1,114	PLASTIC RYNITE 430
85169	984	PLASTIC MARLEX HMN 50100
85170	1,115	PLASTIC RYNITE 940
85171	1,047	PLASTIC PLENCO 04466
85172	1,115	PLASTIC RYNITE 940FB
85173	1,115	PLASTIC RYNITE RF530
85174	1,115	PLASTIC RYNITE FR543
85175	1,115	PLASTIC RYTON R-10 5002C
85176	1,115	PLASTIC RYNITE FR945
85177	1,048	PLASTIC PLENCO 04485
85178	1,115	PLASTIC RYNITE SST35
85179	1,048	PLASTIC PLENCO 04527
85180	1,115	PLASTIC RYTON R-10 5004A
85181	1,133	PLASTIC SURLYN 8020

MSFC-HDBK-527 REV F 9999942 0006827 3

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
85182	1,048	PLASTIC PLENCO 04548
85183	1,133	PLASTIC SURLYN 8528
85184	1,048	PLASTIC PLENCO 04568
85185	1,133	PLASTIC SURLYN 8550
85186	1,133	PLASTIC SURLYN 8660
85187	1,048	PLASTIC PLENCO 05115
85188	1,116	PLASTIC RYTON R-10 7006A
85189	1,133	PLASTIC SURLYN 8920
85190	1,048	PLASTIC PLENCO 05118
85191	1,133	PLASTIC SURLYN 8940
85192	1,048	PLASTIC PLENCO 06201
85193	1,133	PLASTIC SURLYN 9020
85194	1,048	PLASTIC PLENCO 06203
85195	1,133	PLASTIC SURLYN 9450
85196	1,048	PLASTIC PLENCO 06305
85197	1,133	PLASTIC SURLYN 9520
85198	1,134	PLASTIC SURLYN 9650
85199	1,134	PLASTIC SURLYN 9721
85200	1,134	PLASTIC SURLYN 9730
85201	1,134	PLASTIC SURLYN 9910
85202	1,134	PLASTIC SURLYN 9950
85203	1,134	PLASTIC SURLYN 9970
85204	1,116	PLASTIC RYTON R-3
85205	1,240	PLASTIC ZYTEL 109L
85206	1,048	PLASTIC PLENCO 06205
85207	936	PLASTIC HIMOD N66KV20
85208	1,042	PLASTIC PLASKON 1960
85209	1,048	PLASTIC PLENCO 06343
85210	1,048	PLASTIC PLENCO 06553
85211	1,048	PLASTIC PLENCO 06554
85212	1,048	PLASTIC PLENCO 06582/MX582
85213	1,049	PLASTIC PLENCO 07002
85214	1,049	PLASTIC PLENCO 07080
85215	1,049	PLASTIC PLENCO 07200
85216	1,049	PLASTIC PLENCO 07202
85217	1,049	PLASTIC PLENCO 07203
85218	936	PLASTIC HIMOD N6GL40
85219	1,049	PLASTIC PLENCO 07307
85220	1,049	PLASTIC PLENCO 07321
85221	936	PLASTIC HIMOD N6KV20
85222	1,049	PLASTIC PLENCO 07368
85223	1,049	PLASTIC PLENCO 07417
85224	936	PLASTIC HIMOD PCGL40
85225	1,049	PLASTIC PLENCO 07467
85226	936	PLASTIC HIMOD PETGL40
85227	1,049	PLASTIC PLENCO 07476
85228	1,049	PLASTIC PLENCO 07487
85229	936	PLASTIC HIMOD PETGL55
85230	1,045	PLASTIC PLENCO 01505
85231	936	PLASTIC HIMOD PPGL50
85232	1,045	PLASTIC PLENCO 01510
85233	936	PLASTIC HIMOD PUGL40
85234	1,042	PLASTIC PLASKON 1961
85235	936	PLASTIC HIMOD PUKV20
85236	1,315	RUBBER PUGL40
85237	1,042	PLASTIC PLASKON 1974
85238	1,045	PLASTIC PLENCO 01529
85239	1,315	RUBBER PUKV20
85240	1,046	PLASTIC PLENCO 01530
85241	1,046	PLASTIC PLENCO 01535
85242	1,061	PLASTIC POLYPENCO PTFE FLUOROCARBON
85243	1,046	PLASTIC PLENCO 01580
85244	1,042	PLASTIC PLASKON 1985
85245	1,046	PLASTIC PLENCO 01581
85246	1,046	PLASTIC PLENCO 02000
85247	1,194	PLASTIC ULTRA-WEAR UHMUPE
85248	1,042	PLASTIC PLASKON 2060
85249	1,046	PLASTIC PLENCO 02300
85250	1,046	PLASTIC PLENCO 023008
85251	1,063	PLASTIC POLYSAR 101
85252	1,046	PLASTIC PLENCO 02360
85253	1,063	PLASTIC POLYSAR 103
85254	1,046	PLASTIC PLENCO 02408
85255	1,063	PLASTIC POLYSAR 200
85256	1,042	PLASTIC PLASKON 2061
85257	1,046	PLASTIC PLENCO 02482
85258	1,063	PLASTIC POLYSAR 202
85259	1,042	PLASTIC PLASKON 3100
85260	1,063	PLASTIC POLYSAR 203
85261	1,046	PLASTIC PLENCO 02535
85262	1,063	PLASTIC POLYSAR 205
85263	1,046	PLASTIC PLENCO 02567
85264	1,042	PLASTIC PLASKON 3100-7150
85265	1,063	PLASTIC POLYSAR 208
85266	1,046	PLASTIC PLENCO 02571
85267	1,063	PLASTIC POLYSAR 220
85268	1,042	PLASTIC PLASKON 3100LS
85269	1,063	PLASTIC POLYSAR 2220
85270	1,046	PLASTIC PLENCO 02929
85271	1,063	PLASTIC POLYSAR 2400
85272	1,042	PLASTIC PLASKON 3130
85273	1,047	PLASTIC PLENCO 02957
85274	1,063	PLASTIC POLYSAR 3350
85275	1,042	PLASTIC PLASKON 3200
85276	1,063	PLASTIC POLYSAR 415
85277	1,047	PLASTIC PLENCO 03343
85278	1,063	PLASTIC POLYSAR 4220
85279	1,042	PLASTIC PLASKON 3200LS
85280	1,064	PLASTIC POLYSAR 4300
85281	1,042	PLASTIC PLASKON 3200SF
85282	1,047	PLASTIC PLENCO 03509
85283	1,047	PLASTIC PLENCO 03557
85284	1,047	PLASTIC PLENCO 03597
85285	1,047	PLASTIC PLENCO 04002
85286	1,043	PLASTIC PLASKON 3300
85287	1,047	PLASTIC PLENCO 04300
85288	1,043	PLASTIC PLASKON 3300S
85289	1,047	PLASTIC PLENCO 04301
85290	1,043	PLASTIC PLASKON 3300SH
85291	1,047	PLASTIC PLENCO 04304

MSFC-HDBK-527 REV F 9999942 0006828 5

Information Handling Services, 2000

MATCD	PAGE	DESIGNATION
85292	1,043	PLASTIC PLASKON 4020
85293	1,047	PLASTIC PLENCO 04309
85294	1,043	PLASTIC PLASKON 5000
85295	1,047	PLASTIC PLENCO 04349
85296	1,043	PLASTIC PLASKON 5000-7097
85297	1,045	PLASTIC PLENCO 00713
85298	1,045	PLASTIC PLENCO 00714
85299	1,045	PLASTIC PLENCO 00732
85300	1,045	PLASTIC PLENCO 00755
85301	1,045	PLASTIC PLENCO 00757
85302	1,045	PLASTIC PLENCO 01500
85303	1,022	PLASTIC NYLON 7420
85304	1,022	PLASTIC NYLON 7423
85305	1,022	PLASTIC NYLON N186
85306	1,022	PLASTIC NYLON N224
85307	838	PLASTIC CELANEX 2000
85308	838	PLASTIC CELANEX 2000K
85309	839	PLASTIC CELANEX 2002
85310	839	PLASTIC CELANEX 2002K
85311	839	PLASTIC CELANEX 2003K
85312	839	PLASTIC CELANEX 2012
85313	839	PLASTIC CELANEX 3112
85314	839	PLASTIC CELANEX 3200
85315	839	PLASTIC CELANEX 3210
85316	839	PLASTIC CELANEX 3211
85317	839	PLASTIC CELANEX 3300
85318	839	PLASTIC CELANEX 3310
85319	840	PLASTIC CELANEX 3311
85320	840	PLASTIC CELANEX 3400
85321	840	PLASTIC CELANEX 4300
85322	840	PLASTIC CELANEX 4330
85323	840	PLASTIC CELANEX 5300
85324	840	PLASTIC CELANEX 6400
85325	840	PLASTIC CELANEX 7700
85326	840	PLASTIC CELCON AS270
85327	840	PLASTIC CELCON AS450
85328	840	PLASTIC CELCON GB25
85329	840	PLASTIC CELCON GC25A GLASS COUPLED
85330	840	PLASTIC CELCON M25
85331	840	PLASTIC CELCON M270
85332	840	PLASTIC CELCON M90
85334	841	PLASTIC CELCON MC270HM
85335	792	PASTIC CELCON MC90
85336	841	PLASTIC CELCON MC90HM
85337	841	PLASTIC CELCON WR25
85338	841	PLASTIC CELCON WR90
85339	865	PLASTIC DURALOY 2000
85340	865	PLASTIC DURALOY 2100
85341	865	PLASTIC DUREL 400
85342	865	PLASTIC DUREL 410
85343	865	PLASTIC DUREL 420
85344	866	PLASTIC DUREL 430
85345	866	PLASTIC DUREL 440
85346	841	PLASTIC CHEMCOR PARAFFIN EMULSION 135-50
85347	841	PLASTIC CHEMCOR POLY EMULSION 286

MATCD	PAGE	DESIGNATION
85348	243	ADHESIVE SEALUM FM100
85349	243	ADHESIVE SEALUM SM501
85350	243	ADHESIVE SEALUM SM506
85351	243	ADHESIVE SEALUM SM507
85352	244	ADHESIVE SEALUM SM508
85353	244	ADHESIVE SEALUM SM509
85354	244	ADHESIVE SEALUM SM532
85355	875	PLASTIC EA3000
85356	875	PLASTIC EA3100
85357	875	PLASTIC EA3200
85358	186	ADHESIVE LOCTITE 635
85360	17	ADHESIVE ABLEBOND 463-1
85362	814	PLASTIC AKEMI AP2301
85363	1,064	PLASTIC POLYSTYROL 158K
85364	971	PLASTIC LUBRICOMP NYKON R
85365	703	LAMIN EPOXY/GRAPHITE FIBERITE HY-E2030D
85366	564	GASKET TECK SPAN P/N 48-09860
85367	1,411	TAPE 003004SX1014 COLOR 4 ANODIZED ALUMINUM WITH PS ACRYLIC ADHESIVE
85368	49	ADHESIVE AVIMID N COMPOSITE
85369	101	ADHESIVE EA9228 PRIMER
85370	8	ADHESIVE 3977-01 THERMAL EPOXY
85373	683	LACING TAPE STFE-30B
85374	605	INSULATION FOAM BX250/HYPALON COATED
85375	683	LACING TAPE STFE-80B
85378	750	LUBE GREASE TRIBOLUBE 17C
85379	746	LUBE GREASE KRYTOX GPL103
85383	1,413	TAPE ANODIZED ALUMINUM/ACRYLIC PRESSURE SENSITIVE
85384	309	COATING 2A53 EPOXY ON MULTIWIRE CIRCUIT BOARD
85386	1,359	RUBBER SILICONE SE4404U WITH SI02 FILLER
85387	591	INK MARKING UVEXS 105E BLACK
85388	1,296	RUBBER KALREZ 4079 COMPOUND
85389	600	INSULATION BLANKET DP50392 TYPE 8 KAPTON/GLASS
85390	620	INSULATION FOAM MINICELL L200/REFSET RL 4389 COATING
85391	278	ADHESIVE XEA9394 EPOXY
85392	295	CABLE SPLICE NAS1744
85393	407	CONNECTOR ELEC DG123
85394	378	COATING PRIMER CONVERSION CHROMATE
85396	1,263	PRINTED WIRING BOARD COPPER CLAD/POLYIMIDE GLASS/ CAT-L-INK 50-100 MARKING 1 TO 3 MILS THICK/URALANE 5075 CONF
85397	1,412	TAPE 322 AL FOIL/ADHESIVE
85398	591	INK MARKING WE44 RED
85399	671	LABELS THERMOFIT TIE-ON HT TMS CM
85400	718	LAMIN STYRENE/GLASS REXOLITE 2200
85401	1,535	WIRE MAGNET RECTANGULAR POLYVINYL FORMAL COATED CLASS 105 TYPE 2 AND 4
85402	504	FASTENER APLIX 820 NOMEX NON-MELTING HOOK
85403	504	FASTENER APLIX 820 NOMEX NON-MELTING LOOP
85404	504	FASTENER APLIX 820 NOMEX NON-MELTING HOOK AND LOOP
85405	504	FASTENER APLIX 810 POLYESTER LOOP
85406	504	FASTENER APLIX 810 POLYESTER HOOK
85407	590	INK MARKING A423-66 BASE T252-66 CONVERTER

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006829 7

MATCD	PAGE	DESIGNATION
85408	640	INSULATION FOAM RS9412 POLYURETHANE REFSET RL4389 AND RTV 3140 COATED
85409	1,437	TAPE P2650 SILICONE RUBBER NON ADHESIVE
85410	131	ADHESIVE EPOLITE 5313 EPOXY RESIN
85411	1,454	TAPE SCOTCH Y434 5.5 MIL ALUMINUM, 2 MIL TYPE 830 RUBBER ADHESIVE
85412	1,455	TAPE SCOTCH Y435 8 MIL ALUMINUM, 5 MIL TYPE 830 RUBBER ADHESIVE
85413	1,455	TAPE SCOTCH Y436 12 MIL ALUMINUM, 5 MIL TYPE 830 RUBBER ADHESIVE
85414	413	CONNECTOR PLASTIC WTB56SAD11SY-17
85416	865	PLASTIC DRICLAD PVC NORMAL GRADE GRAY COLOR
85417	1,277	RUBBER COHRLASTIC 4032 GLASS REINFORCED SILICONE SHEET
85418	1,279	RUBBER COHRLASTIC X4052 GLASS REINFORCED SILICONE SHEET
85419	709	LAMIN FIBERITE T50/934 GRAPHITE WITH ADHESIVE FILM HT424 AND PRIMER
85420	303	CLAMP 45L83 LOOP WITH SILICONE CUSHION
85421	413	CONNECTOR RECTANGULAR RACK AND PANEL P/N MM22G5-44SK2H AND P/N MMDIP2265-44SL2L
85422	667	LABEL IDENTIFICATION FLEXOFILM CHROME MYLAR WITH NAZDAR MY111 BLACK INK WITH ACRYLIC PS V23 ADHESIVE
85423	229	ADHESIVE REDUX 410NA EPOXY
85425	405	CONNECTOR CIRCUIT BOARD FR4 DOUBLE WIDTH FLIGHT WITH HUMISEL 1B31 ACRYLIC TYPE AR CONFORMAL COATING
85426	719	LAMIN THORNEL P75 2K/ERLX 1962 UNIDIRECTIONAL POLYMERIC RESIN/CARBON
85427	253	ADHESIVE STW53215 PRIMER WITH A187 XYLENE COUPLING AGENT
85428	1,391	SEALANT POLYSULFIDE PR1770
85429	211	ADHESIVE PL430X EPOXY
85430	1,276	RUBBER COHRLASTIC 3111 GLASS REINFORCED SILICONE FILM
85431	1,401	SLEEVING EXPANDO 686 TIGHTWEAVE POLYPHENYLENE SULFIDE
85432	1,391	SEALANT POLYSULFIDE PR1770 FR
85433	294	CABLE HIGH VOLTAGE RUBBER SILICONE INSULATED WITH VITON SLEEVING
85434	1,393	SEALANT SIL-PAD K10 INSULATOR KAPTON XT POLYIMIDE FILM WITH BORON NITRIDE FILLED SILICONE RUBBER
85435	666	LABEL CAUTION FLEXCON MYLAR WITH ACRYLIC PS ADHESIVE V23 WITH NAZDAR MY111 BLACK AND PANTONE 803C FLUORESCENT
85436	1,359	RUBBER SILICONE SE4404U WITH SIO2 FILLER WITH CHOBOND 320 ADHESIVE
85437	1,393	SEALANT SIL-PAD K4 INSULATOR RUBBER WITH KAPTON XT FILM
85438	605	INSULATION FOAM BX443R POLYURETHANE
85439	151	ADHESIVE EPOXY FM73 POLYESTER FILM
85440	640	INSULATION FOAM RS9412 WITH REFSET RL4389 FR COATED
85441	640	INSULATION FOAM RS9412 POLYURETHANE
85442	635	INSULATION FOAM POUR P2801 POLYISOCYANURATE
85444	667	LABEL IDENTIFICATION FLEXOFILM ACRYLIC PS ADHESIVE V23 WITH NAZDAR MY111 BLACK AND MY124 ORANGE INK
85447	474	FABRIC NOMEX HT-45-55 WITH DYE-AQUA-SET TEXTILE INK WITH DC3140 RTV COATING ON ONE EDGE
85448	474	FABRIC NOMEX HT-45-55 WITH DC3140 RTV COATING ON ONE EDGE
85452	353	COATING GRAY 36231 POLYAMIDE EPOXY
85453	327	COATING BLACK 37038 POLYAMIDE EPOXY
85456	1,264	PWB COPPER CLAD GLASS FABRIC EPOXY RESIN FR4 COATED WITH HUMISEAL/INDICATOR MODEL 2495 ATTACHED TO BOARD
85457	1,419	TAPE G148000 VACUUM DEPOSITED ALUMINUM X 0.5 MIL KAPTON X 3P ADHESIVE X 0.9 OUNCE
85460	1,267	RESIN SDP 1A POLYETNER EPOXY WITH PHTHALIC ACID ANHYDRIDE HARDENER
85461	1,267	RESIN SDP 1 SHEET DAMPING MATERIAL
85462	1,267	RESIN SDP 2 BIS PHENOL A DAMPING MATERIAL
85463	1,267	RESIN SDP 3 BROMINATED EPOXY WITH POLYAMIDEAMINE HARDENER
85464	1,267	RESIN SDP 3A BROMINATED EPOXY WITH POLYAMIDEAMINE HARDENER
85465	1,267	RESIN SDP 4 BROMINATED EPOXY WITH POLYOXYARKYLENE POLYAMINE HARDENER
85466	1,267	RESIN SDP 4A BROMINATED EPOXY WITH POLYOXYARKYLENE POLYAMINE HARDENER
85467	1	ABLATOR BTA BOOSTER TROWELLABLE/EC2216/GLASS SPHERE/CORK
85471	658	INSULATION THERMAZIP 577 ALUMINIZED FIBERGLASS FABRIC WITH POLYIMIDE FOAM
85472	1,443	TAPE RL2168A ASBESTOS COATED WITH BUTYL RUBBER
85473	504	FARBIC BALLASTIC NYLON COATED WITH NICKEL
85474	605	INSULATION FOAM BX442R(X1057-137A) POLYURETHANE
85477	1,535	WIRE ELEC WRAPPED IN P2650 SILICONE TAPE
85478	561	FOAM SOUNDFOAM 'M' POLYURETHANE
85479	561	FOAM SOUNDFOAM "HT" POLYIMIDE WITH NOMEX FABRIC FACING
85481	561	FOAM SOUNDFOAM "HT" POLYIMIDE
85482	719	LAMIN THORNEL P75 2K/ERLX 1962 QUASI ISOTROPIC LAYUP
85483	1,277	RUBBER COHRLASTIC 4150 SILICONE/GLASS
85484	1,439	TAPE P670 POLYETHYLENE
85485	1,438	TAPE P427 TEFLON
85486	1,438	TAPE P440 TEFLON/GLASS
85487	1,415	TAPE DL279 SILICONE
85488	707	LAMIN EPOXY/NOMEX R398/F263
85489	101	ADHESIVE EA913NA
85490		DELETED SEE 05148
85491	1,395	SEALANT THREAD LOCKING COMPOUND
85492	592	INK PELIKAN 24 DIACETONE ALCOHOL
85493	1,453	TAPE SCOTCH 968
85495	1,250	POTTING COMPOUND DC4040 FLUOROSILICONE
85496	1,424	TAPE J677 VINYL CLOTH WITH SILICONE ADHESIVE
85497	671	LACING CORD GUDEBROD DPT-H DACRON

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006830 3

MATCD	PAGE	DESIGNATION
85498	600	INSULATION BLANKET DP50392 TYPE 3 MYLAR/KAPTON/ GLASS
85499	1,413	TAPE AR559 WITH SILICONE TRANSFER ADHESIVE
85500	1,401	SLEEVING PVC POLYMER P/N 96M87264-1
85502	466	FABRIC MX2600/FM5504 SILICA PHENOLIC
85503	466	FABRIC MXB6020/FM5755 GLASS PHENOLIC
85504	1,102	PLASTIC ROD METHACRYLATE
85505	1,400	SILICONE RUBBER, TR9904
85506	225	ADHESIVE PRESSURE SENSITIVE
85509	1,332	RUBBER SILICONE CL 3B GR 70
85510	311	COATING 453-4-5/C212 POLYIMIDE EPOXY
85512	1,332	RUBBER SILICONE CL 3A GR 60
85513	774	MOOG A22035 LUBRICANT
85514	1,332	RUBBER SILICONE CL 3B GR 60
85516	1,332	RUBBER SILICONE CL 3B GR 80
85517	1,328	RUBBER SILICONE 950C1569 TOX RATE STUDY
85518	1,327	RUBBER SILICONE 950C1569
85521	103	ADHESIVE EA934 EPOXY
85523	501	FABRIC THERMOGLASS HEAT TREATED
99000		DELETED SEE 80001
99001		DELETED SEE 80002
99002		DELETED SEE 80004
99003		DELETED SEE 80005
99005		DELETED SEE 80006
99006		DELETED SEE 80007
99009		DELETED SEE 80008
99010		DELETED SEE 80009

MATCD	PAGE	DESIGNATION

Information Handling Services, 2000

TABLE 2D

NONMETALS BY MANUFACTURER

Information Handling Services, 2000

DATE: 12/23/88
NON-METALS DESIGNATIONS BY MANUFACTURER

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

MANUFACTURER	DESIGNATION
3D POLYMERS	RUBBER LATEX NATURAL
3M CO	ADHESIVE 1099L
	ADHESIVE 1300 ROLL COATABLE
	ADHESIVE 1751 B/A
	ADHESIVE 1838 B/A TAN
	ADHESIVE 1838L B/A TRANSLUCENT
	ADHESIVE 1870
	ADHESIVE 1P20025 EPOXY CLASS 1
	ADHESIVE 2141
	ADHESIVE 2214 HIGH DENSITY
	ADHESIVE 2214 HIGH FLEX
	ADHESIVE 2214 NON-METALLIC FIELD
	ADHESIVE 2216 B/A FAST CURE TRANSLUCENT
	ADHESIVE 221H-HI
	ADHESIVE 33 RED
	ADHESIVE 34 NEUTRAL
	ADHESIVE 3501 B/A CLEAR
	ADHESIVE 3533 B/A CLEAR
	ADHESIVE 3533 B/A GREY
	ADHESIVE 3570 B/A CLEAR
	ADHESIVE 36 BLACK
	ADHESIVE 37 BLACK SELF EXTINGUISHING
	ADHESIVE 3C #202
	ADHESIVE 3C #203
	ADHESIVE 3C #204
	ADHESIVE 3C #27
	ADHESIVE 3C #DW 205
	ADHESIVE 3C NONETCH FOAM
	ADHESIVE 3C PAN-L-BOND
	ADHESIVE 3C STYROBOND
	ADHESIVE 3C WALLBOND
	ADHESIVE 3M AEROSOL 90
	ADHESIVE 3M AEROSOL SUPER 77N
	ADHESIVE 4323
	ADHESIVE 4550
	ADHESIVE 4799
	ADHESIVE 4914 ACRYLIC
	ADHESIVE 5 GREEN
	ADHESIVE 5 NEUTRAL
	ADHESIVE 5230
	ADHESIVE 583
	ADHESIVE 75
	ADHESIVE 76/KUA FOAM
	ADHESIVE 76/URETHANE FOAM
	ADHESIVE 826
	ADHESIVE 847H
	ADHESIVE 847L
	ADHESIVE 880
	ADHESIVE 959
	ADHESIVE AF126
	ADHESIVE AF126-2-03/06
	ADHESIVE AF131
	ADHESIVE AF143/EC3917 EPOXY FILM
	ADHESIVE AF30
	ADHESIVE AF3002 EPOXY FILM
3M CO	ADHESIVE AF3015
	ADHESIVE AF3024
	ADHESIVE AF31
	ADHESIVE AF42 EPOXY FILM
	ADHESIVE BACON FA8-BA5 COATED WITH SCOTCHCAST 280 B/A
	ADHESIVE CA3
	ADHESIVE CA4
	ADHESIVE CA40
	ADHESIVE CA40H
	ADHESIVE CA5
	ADHESIVE CA7
	ADHESIVE CA8
	ADHESIVE CA9
	ADHESIVE CASE SEALING ADHESIVE EC4365
	ADHESIVE DP100 CLEAR
	ADHESIVE DP105 CLEAR
	ADHESIVE DP110 CLEAR
	ADHESIVE DP110 GRAY
	ADHESIVE DP190 GRAY
	ADHESIVE DUR METAL SUPER-RAPID WEAR RESISTANT
	ADHESIVE EC1022
	ADHESIVE EC1137
	ADHESIVE EC1239 B/A CLASS A 1/2
	ADHESIVE EC1239 B/A CLASS A 1/4
	ADHESIVE EC1239 B/A CLASS A 2
	ADHESIVE EC1239 B/A CLASS A 4
	ADHESIVE EC1239 B/A CLASS B 1/2
	ADHESIVE EC1239 B/A CLASS B 1/4
	ADHESIVE EC1239 B/A CLASS B 2
	ADHESIVE EC1239 B/A CLASS B 4
	ADHESIVE EC1357 NEOPRENE CEMENT
	ADHESIVE EC1386
	ADHESIVE EC1547 B/A
	ADHESIVE EC1828
	ADHESIVE EC1945 A/B
	ADHESIVE EC2158 EPOXY
	ADHESIVE EC2290 EPOXY
	ADHESIVE EC3430
	ADHESIVE EC3500 B/A
	ADHESIVE EC3549 A/B POLYURETHANE
	ADHESIVE EC3569 B/A
	ADHESIVE EC3903
	ADHESIVE EC4500 CHLORINATED ELAST
	ADHESIVE EC776
	ADHESIVE ECP3446
	ADHESIVE EPIBOND 1537
	ADHESIVE EPOXY 77
	ADHESIVE FASTBOND 30 GREEN AND NEUTRAL
	ADHESIVE FASTBOND 30NF GREEN
	ADHESIVE FASTBOND 30NF NEUTRAL
	ADHESIVE FASTBOND 35NF BLUE
	ADHESIVE FASTBOND 38NF BLACK SELF-EXTINGUISHING

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
3M CO	ADHESIVE FASTBOND 4213NF
	ADHESIVE FASTBOND 4268NF
	ADHESIVE FASTBOND 4289NF
	ADHESIVE FASTBOND 42NF
	ADHESIVE FASTBOND 42NF PLUS
	ADHESIVE FASTBOND 45NF CLEAR
	ADHESIVE FASTBOND 45NF ORANGE
	ADHESIVE FASTBOND 47NF CLEAR
	ADHESIVE FASTBOND 4910NF
	ADHESIVE FASTBOND 871NF
	ADHESIVE FASTBOND INSULATION ADHESIVE 33 RED
	ADHESIVE FASTBOND INSULATION ADHESIVE 34 TRANSLUCENT
	ADHESIVE FASTBOND INSULATION ADHESIVE 35NF BLUE
	ADHESIVE FASTBOND INSULATION ADHESIVE 36 BLACK
	ADHESIVE FASTBOND INSULATION ADHESIVE 37 BLACK
	ADHESIVE FASTBOND INSULATION ADHESIVE 38NF BLACK
	ADHESIVE FOAM AF3018 EPOXY
	ADHESIVE HIGH STRENGTH ADHESIVE 90
	ADHESIVE ISOTAC ACRYLIC
	ADHESIVE JET MELT 3735
	ADHESIVE JET MELT 3736
	ADHESIVE JET MELT 3738
	ADHESIVE JET MELT 3740
	ADHESIVE JET MELT 3758
	ADHESIVE JET MELT 3762
	ADHESIVE JET MELT 3764
	ADHESIVE JET MELT 3765
	ADHESIVE JET MELT 3779
	ADHESIVE JET MELT 3783
	ADHESIVE JET MELT 3788
	ADHESIVE JET MELT 3790
	ADHESIVE JET MELT 3792
	ADHESIVE JET MELT 3796
	ADHESIVE JET MELT 3797
	ADHESIVE LABELING ADHESIVE EC4944
	ADHESIVE LIGHTWELD 481
	ADHESIVE PA4887
	ADHESIVE PALLETING ADHESIVE EC4650
	ADHESIVE PANEL AND FOAM #104
	ADHESIVE SCOTCHCAST 208
	ADHESIVE SCOTCHCAST 210
	ADHESIVE SCOTCHCAST 215
	ADHESIVE SCOTCHCAST 216
	ADHESIVE SCOTCHCAST 226
	ADHESIVE SCOTCHCAST 237
	ADHESIVE SCOTCHCAST 241
	ADHESIVE SCOTCHCAST 243
	ADHESIVE SCOTCHCAST 250
	ADHESIVE SCOTCHCAST 252

MANUFACTURER	DESIGNATION
3M CO	ADHESIVE SCOTCHCAST 253
	ADHESIVE SCOTCHCAST 255
	ADHESIVE SCOTCHCAST 260
	ADHESIVE SCOTCHCAST 262
	ADHESIVE SCOTCHCAST 263
	ADHESIVE SCOTCHCAST 265
	ADHESIVE SCOTCHCAST 270
	ADHESIVE SCOTCHCAST 280 A/B
	ADHESIVE SCOTCHCAST 282
	ADHESIVE SCOTCHCAST 3
	ADHESIVE SCOTCHCAST 5064
	ADHESIVE SCOTCHCAST 5140
	ADHESIVE SCOTCHCAST 5166
	ADHESIVE SCOTCHCAST 5235
	ADHESIVE SCOTCHCAST 5237
	ADHESIVE SCOTCHCAST 5240
	ADHESIVE SCOTCHCAST 5241
	ADHESIVE SCOTCHCAST 5242
	ADHESIVE SCOTCHCAST 5243
	ADHESIVE SCOTCHCAST 5326
	ADHESIVE SCOTCHCAST 9
	ADHESIVE SCOTCHGRIP 1099 VINYL
	ADHESIVE SCOTCHGRIP 1300
	ADHESIVE SCOTCHGRIP 1357 NEUTRAL
	ADHESIVE SCOTCHGRIP 1711
	ADHESIVE SCOTCHGRIP 2126
	ADHESIVE SCOTCHGRIP 2210
	ADHESIVE SCOTCHGRIP 2226 GREEN
	ADHESIVE SCOTCHGRIP 4518
	ADHESIVE SCOTCHGRIP 5034 NEUTRAL
	ADHESIVE SCOTCHGRIP 847
	ADHESIVE SCOTCHGRIP 847H
	ADHESIVE SCOTCHGRIP 847L
	ADHESIVE SCOTCHGRIP EC1300L
	ADHESIVE SCOTCHMELT E3861
	ADHESIVE SCOTCHSEAL 1252
	ADHESIVE SCOTCHSEAL 1279
	ADHESIVE SCOTCHSEAL 1792
	ADHESIVE SCOTCHSEAL 1814
	ADHESIVE SCOTCHSEAL 2084
	ADHESIVE SCOTCHSEAL 2084H
	ADHESIVE SCOTCHSEAL 5200
	ADHESIVE SCOTCHSEAL 612
	ADHESIVE SCOTCHSEAL 750
	ADHESIVE SCOTCHSEAL 800
	ADHESIVE SCOTCHSEAL 801 B/A
	ADHESIVE SCOTCHWELD 111
	ADHESIVE SCOTCHWELD 13
	ADHESIVE SCOTCHWELD 1357L
	ADHESIVE SCOTCHWELD 15
	ADHESIVE SCOTCHWELD 1751L
	ADHESIVE SCOTCHWELD 2214 HI DENSITY
	ADHESIVE SCOTCHWELD 2214 HI FLEX
	ADHESIVE SCOTCHWELD 2214 NONMETALLIC
	ADHESIVE SCOTCHWELD 2214HT

MSFC-HDBK-527 REV F 9999942 0006834 0

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
3M CO	ADHESIVE SCOTCHWELD 2262
	ADHESIVE SCOTCHWELD 3501 B/A
	ADHESIVE SCOTCHWELD 3520 B/A
	ADHESIVE SCOTCHWELD 3532 B/A
	ADHESIVE SCOTCHWELD 3533 B/A
	ADHESIVE SCOTCHWELD 3535 B/A
	ADHESIVE SCOTCHWELD 3553 B/A
	ADHESIVE SCOTCHWELD 4060
	ADHESIVE SCOTCHWELD 42
	ADHESIVE SCOTCHWELD 4475
	ADHESIVE SCOTCHWELD 4693
	ADHESIVE SCOTCHWELD 776
	ADHESIVE SCOTCHWELD AF163-205T
	ADHESIVE SCOTCHWELD AF163-24
	ADHESIVE SCOTCHWELD AF163-2K
	ADHESIVE SCOTCHWELD AF163-2M
	ADHESIVE SCOTCHWELD AF191 STRUCTURAL FILM
	ADHESIVE SCOTCHWELD EC1469
	ADHESIVE SCOTCHWELD EC1614
	ADHESIVE SCOTCHWELD EC1648
	ADHESIVE SCOTCHWELD EC1838 B/A
	ADHESIVE SCOTCHWELD EC2214 EPOXY
	ADHESIVE SCOTCHWELD EC2216 B/A
	ADHESIVE SCOTCHWELD EC3420
	ADHESIVE SCOTCHWELD EC3430
	ADHESIVE SCOTCHWELD EC3446
	ADHESIVE SCOTCHWELD EC3448
	ADHESIVE SCOTCHWELD EC588
	ADHESIVE SCOTCHWELD FILM AF10
	ADHESIVE SCOTCHWELD FILM AF111
	ADHESIVE SCOTCHWELD FILM AF13
	ADHESIVE SCOTCHWELD FILM AF147
	ADHESIVE SCOTCHWELD FILM AF202
	ADHESIVE SCOTCHWELD FILM AF32
	ADHESIVE SCOTCHWELD FILM AF6
	ADHESIVE SCOTCHWELD IXA3430
	ADHESIVE SCOTCHWELD IXA3448
	ADHESIVE SCOTCHWELD IXA3537
	ADHESIVE SCOTCHWELD IXA3538
	ADHESIVE SCOTCHWELD IXA3580
	ADHESIVE SCOTCHWELD XA3950
	ADHESIVE SOUNDSEAL ACOUSTICAL #909
	ADHESIVE SPRAY 74
	ADHESIVE SPRAY 76
	ADHESIVE SUPER 77 SPRAY
	ADHESIVE WALLBOARD ADHESIVE #108
	ADHESIVE WEAR RESISTANT LIQUID #11220
	ADHESIVE WEAR RESISTANT PUTTY #11420
	ADHESIVE WEATHERBAN 202
	ADHESIVE WEATHERBAN 404
	ADHESIVE WEATHERBAN 606NF
	ADHESIVE X1160 PS
	ADHESIVE XR5038 EPOXY
	ADHESIVE XR5135 EPOXY
	ADHESIVE Z50 ACRYLIC

MANUFACTURER	DESIGNATION
3M CO	CARTRIDGE DATA DC 300A
	CERAMIC 5656 (INORG)
	CERAMIC AB312 FABRIC/ACRYLIC/FC723
	CERAMIC AB312 FABRIC/POLYSULFONE/FC723
	CERAMIC ALSIMAG 771 (INORG)
	CERAMIC INSULATOR MATERIAL
	CERAMIC NEXTEL XC-568 F12 INOR
	COATING 401 SERIES VELVET POLYESTER
	COATING 401-B2 GRAY
	COATING 401-C10 BLACK
	COATING FLUORAD FC721
	COATING INK/ADHESIVE ON LEXAN
	COATING NEXTEL 3101-C10
	COATING NEXTEL 901P 1
	COATING PRIMER SAFETY WALK
	COATING SCOTCHGARD EC4101-C16
	COATING SCOTCHGARD FC326
	COATING SOLAR ABSORBER ECP2200
	COATING TAPE PRIMER 81
	COATING XR5133 EPOXY
	CONNECTOR SCOTCHFLEX SOCKET
	COOLANT FC-40
	DESICCANT NBR48213
	FABRIC ARGNAMITE GRAPHITE COATED
	FABRIC CERAMIC AB312 SILICONE COATED
	FABRIC CERAMIC AB312 WITH Z6070
	FABRIC DACRON/SILICONE RUBBER SRD5210
	FABRIC DACRON/VITON FD5318
	FABRIC GLASS/ALUMINUM/SILICONE SRGA2218
	FABRIC GLASS/SILICONE SRG1817
	FABRIC NOMEX COATED WITH SCOTCHGARD FC4101
	FABRIC NOMEX-BLUE WITH FC4101-C16
	FABRIC SRGA 0213 ALUM/GLAS/SIL
	FABRICOAT SRGA-0209
	FASTENER SCOTCHMATE DUAL LOCKING TY 400
	FASTENER SCOTCHMATE HOOK SJ3419FR BLACK/ON BLACK NOMEX DUCK
	FASTENER SCOTCHMATE SJ3400 HOOK
	FASTENER SCOTCHMATE SJ3401 LOOP
	FASTENER SCOTCHMATE SJ3402 HOOK
	FASTENER SCOTCHMATE SJ3415 HOOK HS
	FASTENER SCOTCHMATE SJ3418 LOOP FIRE/PR
	FASTENER SCOTCHMATE SJ3419 HOOK FIRE/PR
	FASTENER SCOTCHMATE SJ3441 TY 400
	FASTENER SCOTCHMATE SJ3442 TY 170
	FASTENER SCOTCHMATE SJ3501 SOL/HA ADHESIVE
	FASTENER SCOTCHMATE SJ3502 SOL/HA ADHESIVE
	FASTENER SCOTCHMATE SJ3503 PS ADHESIVE BACK
	FASTENER SCOTCHMATE SJ3504 PS ADHESIVE BACK
	FASTENER SCOTCHMATE SJ3509 HA ADHESIVE BACK
	FASTENER SCOTCHMATE SJ3511 HS ADHESIVE BACK

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
3M CO	FASTENER SCOTCHMATE SJ3514 HA ADHESIVE BACK
	FASTENER SCOTCHMATE SJ3526 HOOK/26 SER
	FASTENER SCOTCHMATE SJ3527 LOOP/26 SER
	FASTENER SCOTCHMATE SJ3528 HOOK/26 SER
	FASTENER SCOTCHMATE SJ3530 HOOK/36 SER
	FASTENER SCOTCHMATE SJ3537 LOOP/36 SER
	FASTENER SCOTCHMATE SJ3538 HOOK/36 SER
	FASTENER SCOTCHMATE SJ3541 TY 400
	FASTENER SCOTCHMATE SJ3542 TY 170
	FASTENER SCOTCHMATE SJ3551 TY 400 PS
	FASTENER SCOTCHMATE SJ3552 TY 170 PS
	FASTENER SCOTCHMATE SJ3571 LOOP PS ADHESIVE
	FASTENER SCOTCHMATE SJ3572 HOOK PS ADHESIVE
	FASTENER VELCRO NYLON LOOP SJ3418 AND HOOK SJ3419B
	FILM 2104 PLASTIC
	FILM 8019,8020 WITH 8060 LABEL
	FILM 8210 WITH 8060 LABEL
	FILM BONDING XC453
	FILM COLORSLIDE 1000/135-36
	FILM PHOTOSENSITIVE SCOTCHCAL
	FILM SCOTT CUSTOM GRADE
	FILM VINYL 3650G INK COATED P/S
	FILTER TYPE G THICKNESS G-0110
	INSULATION 60
	INSULATION FIBERMAT 2539
	INSULATION FOAM POLYETHYLENE/EC2241 COAT
	INSULATION FOAM POLYSTYRENE/KEL-F 90 GREASE COATED
	INSULATION FOAM POLYURETHANE FR
	INSULATION FOAM POLYURETHANE FR6704/EC2241 4PCF
	INSULATION ISOMICA CL20 INORGANIC
	INSULATION POLYESTER FIBERMAT 2538
	INSULATION TG15000/MYLAR/FEP TAPE
	INSULATION TG15000/MYLAR/L-T-80 TAPE
	INSULATION TG15000/SCOTCH 853 TAPE
	INSULATION TG15000/TI/TAPE 853/KAP
	KEL-F 800 MEK/SPRAY
	KEL-F 81
	KEL-F 81 PV 506 GASKET
	KEL-F 81/6061 RESIN
	KEL-F CTFE UNPLASTICIZED
	KEL-F PLASTICIZED
	LABEL 7720/7710/7920/ADHESIVE 400
	LABEL 8060 PLASTIC/POLYESTER BASE
	LABEL IDENTIFICATION MYLAR ADHESIVE 850 CLEAR
	LABEL IDENTIFICATION MYLAR ADHESIVE 850/ RED
	LABEL IDENTIFICATION MYLAR ADHESIVE 850/ SILVER
3M CO	LABEL IDENTIFICATION MYLAR ADHESIVE 853/ CLEAR
	LABEL IDENTIFICATION SCOTCHCAL 8006 RED/ TRANSPARENT
	LABEL IDENTIFICATION SCOTCHCLAD 8005 ADHESIVE/ALUMINUM
	LACING TAPE SCOTCH
	LAMIN EPOXY/BORON SP296
	LAMIN EPOXY/GLASS/SCOTCHCAST 251
	LAMIN SCOTCHPLY 1009-36 EPOXY
	LUBE OIL FLUOROLUBE FS-5
	PAPER DRY SILVER 7772
	PAPER DRY-SILVER TYPE 7771
	PLASTIC 606/21
	PLASTIC 607AA/22NF
	PLASTIC 608-10/12N
	PLASTIC 608-10TLS/12NLS
	PLASTIC 6164-2/21
	PLASTIC 7/308R/N
	PLASTIC POLYPROPYLENE FILTRETE G108
	POTTING COMPOUND EPOXY EC1469
	POTTING COMPOUND SCOTCHCAST 10 EPOXY
	POTTING COMPOUND SCOTCHCAST 212
	POTTING COMPOUND SCOTCHCAST 221
	POTTING COMPOUND SCOTCHCAST 226 A/B
	POTTING COMPOUND SCOTCHCAST 235 EPOXY
	POTTING COMPOUND SCOTCHCAST 247
	POTTING COMPOUND SCOTCHCAST 250 EPOXY.
	POTTING COMPOUND SCOTCHCAST 251
	POTTING COMPOUND SCOTCHCAST 281 EPOXY
	POTTING COMPOUND SCOTCHCAST 5 EPOXY
	POTTING COMPOUND SCOTCHCAST 8
	POTTING COMPOUND SCOTCHCAST 9 EPOXY
	POTTING COMPOUND SCOTCHCAST EC243EPX
	POTTING COMPOUND SCOTCHCAST EC243EPX TOX RATE STUDY
	POTTING COMPOUND SCOTCHCAST XR5001
	POTTING COMPOUND SCOTCHCAST XR5068
	RUBBER BUNA N
	RUBBER BUNA N FC776
	RUBBER FLUOREL 1066
	RUBBER FLUOREL 1079K
	RUBBER FLUOREL 2231
	RUBBER FLUOREL 3217
	RUBBER FLUOREL 4500
	RUBBER FLUOREL 5033
	RUBBER FLUOREL 5767-1
	RUBBER FLUOREL 5823
	RUBBER FLUOREL FC2170
	RUBBER FLUOREL FC2174
	RUBBER FLUOREL V23
	RUBBER SILICONE SRB0607
	SEALANT POLYESTER
	SEALANT POLYSULFIDE EC101
	SEALANT SCOTCHSEAL 3950

MSFC-HDBK-527 REV F 9999942 0006836 4

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
3M CO	SEALANT SCOTCHSEAL EC1103
	SEALANT WEATHERBAN 101 POLYSULFIDE
	STORAGE CAN FOR RECORDING TAPE
	TAPE ANTI-SLIP SAFETY SEE TEST REPORT
	TAPE EDGING 750 ACETATE PAPER WITH ADHESIVE
	TAPE FGA32600 ALUMINIZED
	TAPE HI-TEMP ACRYLIC ADHESIVE
	TAPE L-T-90D/SCOTCH 800
	TAPE LEAD FOIL 420
	TAPE LETTERING 3M
	TAPE POLYESTER 415/ACRYLIC ADHESIVE
	TAPE PTFE SEALANT 48
	TAPE REFLECTIVE
	TAPE SAFETY WALK ANTI-SLIP
	TAPE SCOTCH 1157
	TAPE SCOTCH 1170 ALUMINUM FOIL CONDUCTIVE ACRYLIC ADHESIVE
	TAPE SCOTCH 118 COPPER WITH ACRYLIC ADHESIVE
	TAPE SCOTCH 1181
	TAPE SCOTCH 1245 CU WITH SILICONE ADHESIVE
	TAPE SCOTCH 1267 AL/ACRYLIC/ADHESIVE
	TAPE SCOTCH 27 GLASS/RUBBER/ADHESIVE
	TAPE SCOTCH 3 ELECTRIC
	TAPE SCOTCH 3082 TEFLON
	TAPE SCOTCH 346 DOUBLE COAT PS
	TAPE SCOTCH 361 GLASS/SILICONE/ADHESIVE
	TAPE SCOTCH 363 REFLECTIVE
	TAPE SCOTCH 380 COTTON
	TAPE SCOTCH 390 POLYETHYLENE
	TAPE SCOTCH 425 PS
	TAPE SCOTCH 428 ALUMINUM FOIL/RUBBER ADHESIVE
	TAPE SCOTCH 433 ALUMINUM FOIL WITH SILICONE ADHESIVE
	TAPE SCOTCH 438
	TAPE SCOTCH 444 POLYESTER DOUBLE BACK
	TAPE SCOTCH 465 ACRYLIC TRANSFER
	TAPE SCOTCH 467
	TAPE SCOTCH 468
	TAPE SCOTCH 471
	TAPE SCOTCH 474
	TAPE SCOTCH 48 TEFLON NO ADHESIVE
	TAPE SCOTCH 49
	TAPE SCOTCH 5 POLYESTER
	TAPE SCOTCH 53 POLYESTER
	TAPE SCOTCH 53 POLYURETHANE/SOLITHANE 113/300
	TAPE SCOTCH 54 POLYESTER PS
	TAPE SCOTCH 5413 KAPTON WITH SILICONE ADHESIVE
	TAPE SCOTCH 5451
	TAPE SCOTCH 5453 TFE/SILICONE/GLASS
	TAPE SCOTCH 5480 TEFLON
3M CO	TAPE SCOTCH 5491 SILICONE
	TAPE SCOTCH 56 POLYESTER
	TAPE SCOTCH 567
	TAPE SCOTCH 57 POLYESTER
	TAPE SCOTCH 583 ACRYLIC ADHESIVE
	TAPE SCOTCH 6 ACETATE
	TAPE SCOTCH 60 TFE TEFLON/SILICONE
	TAPE SCOTCH 61 TFE/SILICONE PS
	TAPE SCOTCH 62 TFE/SILICONE PS ADHESIVE
	TAPE SCOTCH 63
	TAPE SCOTCH 635 POLYESTER
	TAPE SCOTCH 64 TFE/GLASS/SILICONE
	TAPE SCOTCH 666 PVC ACRYLIC ADHESVIE
	TAPE SCOTCH 69 GLASS/SILICONE/ADHESIVE
	TAPE SCOTCH 74 POLYESTER/RUBBER
	TAPE SCOTCH 75-4280-0501-3-8005/ADHESIVE
	TAPE SCOTCH 79 FIBERGLASS
	TAPE SCOTCH 800 TEFLON PRESCRIPTION
	TAPE SCOTCH 8210 LABEL GUARD
	TAPE SCOTCH 838 TEDLAR
	TAPE SCOTCH 8417 CLEAR/8418 OPAQUE
	TAPE SCOTCH 850 POLYESTER/ACRYLIC ADHESIVE
	TAPE SCOTCH 853 POLYESTER
	TAPE SCOTCH 92 SILICONE/POLYMIDE BACKING
	TAPE SCOTCH 950 ACRYLIC TRANSFER
	TAPE SCOTCH 968
	TAPE SCOTCH MAGIC TRANSPARENT
	TAPE SCOTCH X1169 MYLAR RUBBER ADHESIVE
	TAPE SCOTCH X1170
	TAPE SCOTCH X1181
	TAPE SCOTCH X1205 KAPTON WITH ACRYLIC ADHESIVE
	TAPE SCOTCH X1252 POLYESTER PS ADHESIVE
	TAPE SCOTCH Y427 ALUMINUM WITH ACRYLIC ADHESIVE
	TAPE SCOTCH Y434 5.5 MIL ALUMINUM, 2 MIL TYPE 830 RUBBER ADHESIVE
	TAPE SCOTCH Y434 SOUNDDAMP ALUMINUM FOIL
	TAPE SCOTCH Y435 8 MIL ALUMINUM, 5 MIL TYPE 830 RUBBER ADHESIVE
	TAPE SCOTCH Y436 12 MIL ALUMINUM, 5 MIL TYPE 830 RUBBER ADHESIVE
	TAPE SCOTCH Y9360
	TAPE SCOTCH Y9415 POLYESTER ACRYLIC ADHESIVE
	TAPE SCOTCH Y9460 TRANSFER
	TAPE SCOTCH Y9469 ACRYLIC TRANSFER
	TAPE SCOTCH Y9473 TRANSFER
	TAPE SCOTCH Y9485
	TAPE SCOTCH Y966 ACRYLIC TRANSFER
	TAPE SCOTCH YR364 ALUMINUM GLASS WITH SILICONE ADHESIVE
	TAPE SCOTCHCAL 30 MYLAR
	TAPE SCOTCHCAL 3623 VINYL ORANGE
	TAPE SCOTCHCAL 3627 VINYL GREEN

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
3M CO	TAPE SCOTCHCAL 3650
	TAPE SCOTCHCAL 3651 RED
	TAPE SCOTCHCAL 3652 VINYL YELLOW
	TAPE SCOTCHCAL 3658 VINYL GRAY
	TAPE SCOTCHCAL 3930
	TAPE SCOTCHCAL 530 MYLAR
	TAPE SCOTCHCAL 5690 VINYL
	TAPE SCOTCHCAL 639
	TAPE SCOTCHCAL 8010 GREEN TRANSPARENT
	DYNAMARK
	TAPE SCOTCHCAL 8014 BLUE TRANSPARENT
	DYNAMARK
	TAPE SCOTCHCAL 8015
	TAPE SCOTCHLITE 3270 VINYL PS
	TAPE SCOTCHLITE 3290 VINYL PS
	TAPE SCOTCHLITE 680 WITH CTRL TAC
	TAPE SCOTCHLITE 7610 VINYL P/S
	TAPE SCOTCHLITE 8850
	TAPE SCOTCHMARK 7883 POLYESTER
	TAPE SCOTCHMOUNT 4032
	TAPE SCOTCHMOUNT 4408
	TAPE SCOTCHSEAL 3655 VINYL BLACK
	TAPE STOMASEAL 1522 PS
	TAPE VIDEO 400 BLACK
	TAPE VIDEO RCA 3M361
	TAPE VIDEO RCA 3M400
	TAPE/DISPENSER VINYL/PVAC
	TUBING ECC POLYOLEFIN HS
	VELOSTAT 1810 SERIES
	WEBBING STRAP NYLON/FC4101
	ZIPPER NOMEX/BRASS FIRE/WATER PROOF
3M CO/ELECTRICAL DIV	TUBING FLUOROELASTOMER HS
	TUBING FP301 INSULTITE HST
	TUBING FP301 TYPE 2 POLYOLEFIN HS
	TUBING INSULTITE KYNAR HST CLEAR NOC
	TUBING INSULTITE VFP876 HST BLACK
	TUBING VITON HST
3M CO/ROCKWELL	CABLE TIES NOMEX/POLYETHYLENE FC4101
3M CO/SCOTCHCAST	POTTING COMPOUND SCOTCHCAST 8/DC3140
3M CO/SOUTHERN MILLS	FASTENER SCOTCHMATE LOOP SJ3418FR ON BLACK
	NOMEX DUCK 7.5 OZ
A & M ENGINEERING	LAMIN EPOXY/GLASS
A B BOYD	RUBBER SILICONE CL 3B GR 50
A D LITTLE	ADHESIVE 18540 11C/EPON H2 CURE
	FABRIC NEOPRENE/NYLON 18540-33
	RUBBER VITON 133 ELASTOMER
	TAPE NOMEX UTILITY FR PS ADHESIVE
A E NATHAN	FABRIC COTTON 7 OZ/LINING 4 OZ FR
A E PETSCHE CO	INSULATION WIRE POLYOLEFIN/KYNAR
	WIRE ELEC PTFE/GLASS FEP
	WIRE ELEC TFE MINERAL FILLED
A G BAUER	ADHESIVE LEKUTHERM X227
A H RICE	CORD PARACHUTE NYLON
A M PLASTICS	KEL-F CTFE UNPLASTICIZED
A SCHULMAN INC	PLASTIC FORMION FI105

MANUFACTURER	DESIGNATION
A SCHULMAN INC	PLASTIC FORMION FI107
	PLASTIC FORMION FI120
	PLASTIC FORMION FI139
	PLASTIC FORMION FI147
	PLASTIC FORMION FI217
	PLASTIC FORMION FI241
	PLASTIC FORMION FI280
	PLASTIC POLYFLAM RCP762
	PLASTIC POLYFLAM RCP770C
	PLASTIC POLYFLAM RHD260ND (E)
	PLASTIC POLYFLAM RHD260ND RLP426
	PLASTIC POLYFLAM RMS424
	PLASTIC POLYFLAM RMS424E
	PLASTIC POLYFLAM RPP1021
	PLASTIC POLYFLAM RPP1058
	PLASTIC POLYFLAM RPP1062C
	PLASTIC POLYFLAM RPP1174
	PLASTIC POLYFLAM RPP932
	PLASTIC POLYFLAM RPP958
	PLASTIC POLYFLAM RPP958E
	PLASTIC POLYFLAM RPP982
	PLASTIC POLYFLAM RPP985
	PLASTIC POLYFLAM RS425C3
	PLASTIC POLYFORT FPP1006
	PLASTIC POLYFORT FPP1007
	PLASTIC POLYFORT FPP1182
	PLASTIC POLYFORT FPP1200
	PLASTIC POLYFORT FPP1223
	PLASTIC POLYFORT FPP1227
	PLASTIC POLYFORT FPP1237
	PLASTIC POLYFORT FPP1244
	PLASTIC POLYFORT FPP1245
	PLASTIC POLYFORT FPP1257
	PLASTIC POLYFORT FPP1272
	PLASTIC POLYFORT FPP1309
	PLASTIC POLYFORT FPP1310
	PLASTIC POLYFORT FPP1337
	PLASTIC POLYFORT FPP1345
	PLASTIC POLYFORT FPP1383
	PLASTIC POLYFORT FPP1488
	PLASTIC POLYFORT FPP1494
	PLASTIC POLYFORT FPP1512
	PLASTIC POLYFORT FPP1564
	PLASTIC POLYFORT FPP1578
	PLASTIC POLYFORT FPP1607
	PLASTIC POLYFORT FPP1608
	PLASTIC POLYFORT FPP1609
	PLASTIC POLYFORT FPP1611
	PLASTIC POLYFORT FPP1612
	PLASTIC POLYFORT FPP1650
	PLASTIC POLYFORT FPP1651
	PLASTIC POLYFORT FPP1652
	PLASTIC POLYFORT FPP1653
	PLASTIC POLYFORT FPP1654
	PLASTIC POLYFORT FPP1666

MSFC-HDBK-527 REV F 9999942 0006838 8

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
A SCHULMAN INC	PLASTIC POLYFORT PP1531
	PLASTIC POLYFORT PP1549
	PLASTIC POLYFORT PP828
	PLASTIC POLYFORT PP829
	PLASTIC POLYMAN 506
	PLASTIC POLYMAN 507
	PLASTIC POLYMAN 508
	PLASTIC POLYMAN 509
	PLASTIC POLYMAN 510
	PLASTIC POLYMAN 511
	PLASTIC POLYMAN 526
	PLASTIC POLYMAN 551
	PLASTIC POLYMAN 552
	PLASTIC POLYMAN 554
	PLASTIC POLYMAN 558
	PLASTIC POLYTROPE TPP1201
	PLASTIC POLYTROPE TPP293
	PLASTIC POLYTROPE TPP300
	PLASTIC POLYTROPE TPP309
	PLASTIC POLYTROPE TPP313
	PLASTIC POLYTROPE TPP317
	PLASTIC POLYTROPE TPP318
	PLASTIC POLYTROPE TPP319
	PLASTIC POLYTROPE TPP320
	PLASTIC POLYTROPE TPP334
	PLASTIC POLYTROPE TPP336
	PLASTIC POLYTROPE TPP337
	PLASTIC POLYTROPE TPP338
	PLASTIC POLYTROPE TPP341
	PLASTIC POLYTROPE TPP377
	PLASTIC POLYTROPE TPP393
	PLASTIC POLYTROPE TPP394
	PLASTIC POLYTROPE TPP402
	PLASTIC POLYTROPE TPP403
	PLASTIC POLYTROPE TPP408
	PLASTIC POLYTROPE TPP409
	PLASTIC POLYTROPE TPP414
	PLASTIC POLYTROPE TPP420
	PLASTIC POLYTROPE TPP421
	PLASTIC POLYTROPE TPP425
	PLASTIC POLYTROPE TPP427
	PLASTIC POLYTROPE TPP433
	PLASTIC POLYTROPE TPP442
	PLASTIC POLYTROPE TPP443
	PLASTIC POLYTROPE TPP444
	PLASTIC POLYTROPE TPP445
	PLASTIC POLYTROPE TPP446
	PLASTIC POLYTROPE TPP447
	PLASTIC POLYVIN 4507
	PLASTIC POLYVIN 5004
	PLASTIC POLYVIN 5023
	PLASTIC POLYVIN 5514
	PLASTIC POLYVIN 5802
	PLASTIC POLYVIN 5813
	PLASTIC POLYVIN 5819
A SCHULMAN INC	PLASTIC POLYVIN 5824
	PLASTIC POLYVIN 6110
	PLASTIC POLYVIN 6415
	PLASTIC POLYVIN 6424
	PLASTIC POLYVIN 6588
	PLASTIC POLYVIN 6614
	PLASTIC POLYVIN 6618
	PLASTIC POLYVIN 6713
	PLASTIC POLYVIN 6820
	PLASTIC POLYVIN 6825
	PLASTIC POLYVIN 6837
	PLASTIC POLYVIN 7112
	PLASTIC POLYVIN 7125
	PLASTIC POLYVIN 7180
	PLASTIC POLYVIN 7280
	PLASTIC POLYVIN 7427
	PLASTIC POLYVIN 7522
	PLASTIC POLYVIN 7532
	PLASTIC POLYVIN 7601
	PLASTIC POLYVIN 7709
	PLASTIC POLYVIN 7856
	PLASTIC POLYVIN 7911
	PLASTIC POLYVIN 8058
	PLASTIC POLYVIN 8101
	PLASTIC POLYVIN 8110
	PLASTIC POLYVIN 8111
	PLASTIC POLYVIN 8124
	PLASTIC POLYVIN 8125
	PLASTIC POLYVIN 8222
	PLASTIC POLYVIN 8380
	PLASTIC POLYVIN 8384
	PLASTIC POLYVIN 8428
	PLASTIC POLYVIN 8540
	PLASTIC POLYVIN 8546
	PLASTIC POLYVIN 8612
	PLASTIC POLYVIN 8803
	PLASTIC POLYVIN 8813
	PLASTIC POLYVIN 8819
	PLASTIC POLYVIN 8820
	PLASTIC POLYVIN 8822
	PLASTIC POLYVIN 8835
	PLASTIC POLYVIN 9009
	PLASTIC POLYVIN 9044
	PLASTIC POLYVIN 9108
	PLASTIC POLYVIN 9226
	PLASTIC POLYVIN 9400
	PLASTIC POLYVIN 9533
	PLASTIC SUPEROHM 3728
A T CROSS CO	PEN CROSS 3504/REFILL 8543
A W CHESTERTON	SEALANT VANWAY FEP TEFLON O-RING
A W FABER	INK 4025/JCP K10 YELLOW
	INK 4085/JCP K10 RED
	INK 4115/JCP K10 VIOLET
	INK 4145/JCP K10 BLUE
	INK 4205/JCP K10 GREEN

MANUFACTURER	DESIGNATION
A W FABER	INK 4295/JCP K10 BROWN
	INK 4415/JCP K10 BLACK
AIRESEARCH	RUBBER SILICONE EMS342
	RUBBER SILICONE EMS9300
AAI PRODUCTS	INSULATION MATERIAL 550-02 QUARTZ FIBER
ABBOTT LABS	RUBBER LATEX FAULTLESS
	RUBBER LATEX NATURAL
ABLE INDUS	SPONGE RUBBER SILICONE
ABLESTIK	ADHESIVE A HMS16-1443 EPOXY
	ADHESIVE ABLEBOND 150-6 EPOXY
	ADHESIVE ABLEBOND 16-1
	ADHESIVE ABLEBOND 161-3
	ADHESIVE ABLEBOND 163-4
	ADHESIVE ABLEBOND 184-1
	ADHESIVE ABLEBOND 185 EPOXY
	ADHESIVE ABLEBOND 190-3
	ADHESIVE ABLEBOND 190-8
	ADHESIVE ABLEBOND 204-2
	ADHESIVE ABLEBOND 224-1
	ADHESIVE ABLEBOND 293-1
	ADHESIVE ABLEBOND 342-13 ACC
	ADHESIVE ABLEBOND 342-3
	ADHESIVE ABLEBOND 36-2 EPOXY
	ADHESIVE ABLEBOND 369-3 CONDUCTIVE
	ADHESIVE ABLEBOND 380-5
	ADHESIVE ABLEBOND 408-3
	ADHESIVE ABLEBOND 41-1 EPOXY
	ADHESIVE ABLEBOND 410-1
	ADHESIVE ABLEBOND 414-1
	ADHESIVE ABLEBOND 463-1
	ADHESIVE ABLEBOND 463-1 EPOXY/AG FI11
	ADHESIVE ABLEBOND 58-1
	ADHESIVE ABLEBOND 601-1C
	ADHESIVE ABLEBOND 606-2
	ADHESIVE ABLEBOND 66-1
	ADHESIVE ABLEBOND 681-14
	ADHESIVE ABLEBOND 69-5
	ADHESIVE ABLEBOND 71-1LMI
	ADHESIVE ABLEBOND 724-14C
	ADHESIVE ABLEBOND 731-1 EPOXY
	ADHESIVE ABLEBOND 77-1
	ADHESIVE ABLEBOND 770-6 EPOXY
	ADHESIVE ABLEBOND 773-2 BRS
	ADHESIVE ABLEBOND 783-1 EPOXY
	ADHESIVE ABLEBOND 789-3
	ADHESIVE ABLEBOND 789-4
	ADHESIVE ABLEBOND 793-3 EPOXY
	ADHESIVE ABLEBOND 826-1
	ADHESIVE ABLEBOND 84-1A
	ADHESIVE ABLEBOND 84-1LMI
	ADHESIVE ABLEBOND 84-1LMI S1
	ADHESIVE ABLEBOND 84-3
	ADHESIVE ABLEBOND 843-1
	ADHESIVE ABLEBOND 843-4
	ADHESIVE ABLEBOND 85-1

MANUFACTURER	DESIGNATION
ABLESTIK	ADHESIVE ABLEBOND 862-7
	ADHESIVE ABLEBOND 868-3
	ADHESIVE ABLEBOND 877-1
	ADHESIVE ABLEBOND 88-1
	ADHESIVE ABLEBOND 883-1
	ADHESIVE ABLEBOND 883-4
	ADHESIVE ABLEBOND 931-1
	ADHESIVE ABLEBOND 933-1
	ADHESIVE ABLEBOND 941-3
	ADHESIVE ABLEBOND 957-2
	ADHESIVE ABLEBOND 968-2
	ADHESIVE ABLEBOND 969-1
	ADHESIVE ABLEBOND ECF564A
	ADHESIVE ABLEBOND SG2001
	ADHESIVE ABLEBOND SG2002
	ADHESIVE ABLEFILM 501
	ADHESIVE ABLEFILM 504 EPOXY
	ADHESIVE ABLEFILM 517
	ADHESIVE ABLEFILM 546 KAPTON
	ADHESIVE ABLEFILM 550 EPOXY
	ADHESIVE ABLEFILM 550K
	ADHESIVE ABLEFILM 551 EPOXY
	ADHESIVE ABLEFILM 561
	ADHESIVE ABLEFILM 561/40% FILLED
	ADHESIVE ABLEFILM 561K
	ADHESIVE ABLEFILM 563
	ADHESIVE ABLEFILM 563K
	ADHESIVE ABLEFILM 564A
	ADHESIVE ABLEFILM 564K
	ADHESIVE ABLEFILM ECF550
	ADHESIVE ABLEFILM ECF561
	ADHESIVE ABLEFILM ECF563
	ADHESIVE ABLEFOAM 1 EPOXY
	ADHESIVE ABLETHERM 12-1 SILICONE
	ADHESIVE ABLETHERM 8-2
	CABLE COAX SILVER PLATED COPPER WITH PTFE KAPTON
	POTTING COMPOUND ABLECAST 402
ABSCOA INDUSTRIES	TEFLON TFE VIRGIN
ACCESSIBLE PRODUCTS	INSULATION THERMAZIP 577 ALUMINIZED FIBERGLASS FABRIC WITH POLYIMIDE FOAM
ACCRATRONICS	TEFLON TFE/15% GRAPHITE
ACCUTEC	INK PEN ACCUTEC
ACE RUBBER CO	RUBBER SILICONE CL 3A GR 25
	RUBBER SILICONE CL 3B GR 30
ACHESON COLLOIDS	COATING DAG195 CONDUCTIVE
	COATING EMRALON 330
	LUBE DRY DAG 206 MOS2 INORGANIC
	LUBE DRY DAG 213 DISPERSION
	LUBE DRY DAG 217 DISPERSION
	LUBE DRY DAG 250 ORGANIC BINDR
	LUBE DRY DAG 258 MOS2
	LUBE DRY GP1904
	LUBE EMRALON 314 A/B
	LUBE EMRALON 320 A/B

MSFC-HDBK-527 REV F 9999942 0006840 6

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
ACHESON COLLOIDS	LUBE EMRALON 334
	LUBE EMRALON 337
ACME CHEMICALS & INSULATION CO	ADHESIVE E-SOLDER 3012
	ADHESIVE E-SOLDER 3017
	ADHESIVE E-SOLDER 3021
	ADHESIVE E-SOLDER 3022
	ADHESIVE E-SOLDER 3025
	ADHESIVE E-SOLDER 3026
	ADHESIVE E-SOLDER 3044
	ADHESIVE E-SOLDER 3056
	ADHESIVE E-SOLDER 3069
	ADHESIVE E-SOLDER 3083
	ADHESIVE E-SOLDER 320S
	ADHESIVE MARASET RESIN 532C
	ADHESIVE MARASET RESIN 532F
	ADHESIVE MARASET RESIN 536
	ADHESIVE MARASET RESIN 537
	PLASTIC 13N/680
	PLASTIC 13N/HH5
	PLASTIC 606/21
	PLASTIC 607AA/22NF
	PLASTIC 608-10/12N
	PLASTIC 608-10TLS/12NLS
	PLASTIC 610/680
	PLASTIC 610V/901
	PLASTIC 612B/22NF
	PLASTIC 6164-2/21
	PLASTIC 616N/681
	PLASTIC 616N/901
	PLASTIC 618/900C
	PLASTIC 622/680
	PLASTIC 622/GE
	PLASTIC 638/45
	PLASTIC 6410R/H
	PLASTIC 655/555
	PLASTIC 658/558
	PLASTIC 670/70
	PLASTIC 676F/86
	PLASTIC 677F/70
	PLASTIC 7/308R/N
	PLASTIC F18 R/H
	PLASTIC F180R/F181H
	PLASTIC HOMOPOLYMER PVC RESIN VC54
	PLASTIC M53R/H
	PLASTIC MARASET 13N
	PLASTIC MARASET 606
	PLASTIC MARASET 607AA
	PLASTIC MARASET 608-10TLS
	PLASTIC MARASET 610
	PLASTIC MARASET 610V
	PLASTIC MARASET 612B
	PLASTIC MARASET 6164-2
	PLASTIC MARASET 616N
	PLASTIC MARASET 618
	PLASTIC MARASET 622
ACME CHEMICALS & INSULATION CO	PLASTIC MARASET 641D
	PLASTIC MARASET 670L
	PLASTIC MARASET 676F
	PLASTIC MARASET 677F
	PLASTIC MARASET 7-308
	PLASTIC MARASET F18
	PLASTIC MARASET F180R
	PLASTIC MARASET M53
ACTRONICS INC	FILLER ACTROFILL 1241
ADEL	CLAMP WITH SILICONE INSERT
	FABRIC FIBERGLASS SILICONE/7010
	TEFLON G-83 TFE
ADELL PLASTICS	PLASTIC ADELL AB14
	PLASTIC ADELL AB16
	PLASTIC ADELL AB18
	PLASTIC ADELL AF10-660
	PLASTIC ADELL AF10-667
	PLASTIC ADELL AF10-667A
	PLASTIC ADELL AF10-667B
	PLASTIC ADELL AG16-662
	PLASTIC ADELL AH18
	PLASTIC ADELL AL18
	PLASTIC ADELL AM10
	PLASTIC ADELL AN38
	PLASTIC ADELL AO16
	PLASTIC ADELL AR13
	PLASTIC ADELL AR14
	PLASTIC ADELL AR16
	PLASTIC ADELL AR18
	PLASTIC ADELL AT13
	PLASTIC ADELL AT14
	PLASTIC ADELL AT16
	PLASTIC ADELL BH18
	PLASTIC ADELL BL18
	PLASTIC ADELL BR13
	PLASTIC ADELL BR14
	PLASTIC ADELL BR16
	PLASTIC ADELL BR18
	PLASTIC ADELL BR310
	PLASTIC ADELL BY10
	PLASTIC ADELL EF10
	PLASTIC ADELL EP14
	PLASTIC ADELL EP16
	PLASTIC ADELL ER14
	PLASTIC ADELL ER16
	PLASTIC ADELL HR36
	PLASTIC ADELL KR14
	PLASTIC ADELL KR16
	PLASTIC ADELL KR18
ADHESIVE ENGINEERING CO	ADHESIVE CONCRESIVE
	ADHESIVE CONCRESIVE 1064
	ADHESIVE CONCRESIVE 1170
	ADHESIVE CONCRESIVE 1305
	ADHESIVE CONCRESIVE 1310
	ADHESIVE CONCRESIVE 1411

MSFC-HDBK-527 REV F 9999942 0006841 8

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
ADHESIVE ENGINEERING CO	ADHESIVE CONCRESIVE 1419
	ADHESIVE CONCRESIVE 1422
	ADHESIVE CONCRESIVE 1438
	ADHESIVE CONCRESIVE 1440
	ADHESIVE CONCRESIVE 1441
	ADHESIVE CONCRESIVE 3007
	ADHESIVE CONCRESIVE 3008
	ADHESIVE CONCRESIVE 3009
	ADHESIVE CONCRESIVE 3013
	ADHESIVE CONCRESIVE 3014
	ADHESIVE CONCRESIVE 3034
	ADHESIVE CONCRESIVE 3042 PENSEAL 50
	ADHESIVE CONCRESIVE AEX1470
	ADHESIVE CONCRESIVE AEX1482X
	ADHESIVE CONCRESIVE AEX1533G
	ADHESIVE CONCRESIVE AEX1539G
	ADHESIVE CONCRESIVE GLOSSFIX 1409
	ADHESIVE PEN SEAL 50
	CONCRESIVE 1001
	CONCRESIVE 1001 LPL
	CONCRESIVE 1442
	CONCRESIVE 3012
	CONCRESIVE AEX 1482-0
ADHESIVE RESEARCH CORP	TAPE AR559 WITH SILICONE TRANSFER ADHESIVE
ADM TRONICS	ADHESIVE 286
	ADHESIVE 626N
	ADHESIVE AQUAFORTE 108W
	ADHESIVE POLAQUA 103L
	ADHESIVE POLAQUA 123-07
	ADHESIVE POLAQUA 127-07
ADTECH	RUBBER VITON FLUID RESISTANT
	RUBBER VITON O-RING
ADVANCE RUBBER CO	RUBBER VITON CPD 8760
ADVANCE SEAL	ELASTOMER PNF
	RUBBER VITON O-RING V835-75
ADVANCED COATINGS	ADHESIVE 501 NEOPRENE
	COATING POLYURETHANE ORANGE INTL 12197
	COATING URAMET 4-1W-12 #100 GRIT
ADVANCED EXCELLO PROCESS/DOW CORNING	FABRIC NOMEX HT-45-55 WITH DC3140 RTV COATING ON ONE EDGE
	FABRIC NOMEX HT-45-55 WITH DYE-AQUA-SET
	TEXTILE INK WITH DC3140 RTV COATING ON ONE EDGE
ADVANCED INK INC	INK RETARDER PAT715/T950
ADVANCED NETTING	FABRIC MARQUISETTE NYLON N-44
	SCREEN POLYESTER/PVC COATED MESH
ADVANCED POLYMER IND	POTTING COMPOUND EPOXY AP1371 A/B
ADVANCED PROCESS	COATING POLYURETHANE 100 EPOXY WHITE
	COATING POLYURETHANE 710 EPOXY BLACK
AEG-KASSEL	COATING POLYURETHANE LACK181/3
AEROFAB	LAMIN EPOXY/GLASS FF91
AEROMAT PLASTICS	KEL-F 81
	PLASTIC ASTRAGLAS K
	PLASTIC ASTRAGLAS N
	PLASTIC ASTRAGLAS NG
AEROMAT PLASTICS	PLASTIC ESTRALON PET
	PLASTIC GLASBORD S
	PLASTIC LUCITE CAST ACRYLIC
	PLASTIC NYLATRON NSB NYLON
	PLASTIC NYLATRON NSN NYLON
	PLASTIC POLY-GLAZ SHEET
	PLASTIC POLYPENCO 101 (NYLON 6/6)
	PLASTIC POLYPENCO 11
	PLASTIC POLYPENCO 12
	PLASTIC VIVAK SHEET
AEROQUIP	HOSE TEFLON WITH STEEL
	LINER HOSE AE 116-8/AE 121-4
	LINER HOSE AE 246-10/667-16
	TEFLON TFE VIRGIN
AEROSPACE AVIONICS	COATING ENAMEL GREY
AEROSPACE LUBRICANTS	LUBE GREASE AIRCRAFT
	LUBE GREASE TRIBOLUBE 10
	LUBE GREASE TRIBOLUBE 10C
	LUBE GREASE TRIBOLUBE 15
	LUBE GREASE TRIBOLUBE 15MS
	LUBE GREASE TRIBOLUBE 15RP
	LUBE GREASE TRIBOLUBE 16
	LUBE GREASE TRIBOLUBE 17C
AEROSTAT	RUBBER SILICONE HARDNESS SHORE "A" 35-45
AFTON PLASTICS	KEL-F 81
	KEL-F CTFE UNPLASTICIZED
	PLASTIC AM400 (PCTFE)
	PLASTIC DAIKIN TEFLON FEP NP30
	PLASTIC NEOFLON PFA AP210
	PLASTIC NEOFLON PFA AP230
	PLASTIC TEFZEL 200
	PLASTIC TEFZEL 210
	PLASTIC TEFZEL 280
	PLASTIC VIXTRIX 450 CA30
	PLASTIC VIXTRIX 450G
	PLASTIC VIXTRIX 450GL30
	PLASTIC VIXTRIX D150CA30
	PLASTIC VIXTRIX D150G
	PLASTIC VIXTRIX D150GL30
	TEFLON FEP
	TEFLON TFE/25% GLASS
AGC INC	BLADDER BUTYL RUBBER
	GASKET 9-210-6B SILICONE
	RUBBER AGC 3-126 CLASS 5
	RUBBER SYNTHETIC 11-102-1
	RUBBER VITON FLUID RESISTANT
AGFA-GEVAERT	FILM XRS1000 AGFA COLOR
AIN PLASTICS	LAMIN EPOXY/GLASS
	PLASTIC LEXAN 3413 30% GLASS
AIR CRUISERS CO	FABRIC ALUMINIZED M11678 NEOPRENE KEVLAR COATED WITH POLYURETHANE OC
	FABRIC M11673/NYLON/URETHANE
AIR-LOCK INC	KEL-F 81
	LAMIN EPOXY/GLASS RP4002A
	LINER GLASS CLOTH 120/EPON 815

MSFC-HDBK-527 REV F 9999942 0006842 T

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
AIRBORN INC	CONNECTOR PC BOARD WTB90PR-7SY-X/WTB90SED-9SY-X
	CONNECTOR PLASTIC WTB56SAD11SY-17
AIRCO CRYOGENICS	TEFLON RING PISTON RIDER
AIRCRAFT POROUS MEDIA	FABRIC POLYPROPYLENE 3X5WHDC
	FABRIC POLYPROPYLENE 4X5 WHDC
	FILTER MEDIA BACTERIA
AIRCRAFT PRODUCTS	ADHESIVE DAPCOTAC 3001
	FABRIC GLASS SILICONE SMC1050
	FABRIC SILICONE/NYLON H565
AIRCRAFT SEAL	RUBBER SILICONE EXTREME LOW TEMPERATURE LOW TEMPERATURE HARDNESS SHORE "A" 65-75
AIRTEX	LACING TAPE 217
	LACING TAPE AIR-TEX 17
AKEMI PLASTICS	ADHESIVE AP1400
	ADHESIVE AP2108
	ADHESIVE AP2110
	ADHESIVE AP2118 HI-TEMP
	ADHESIVE AP2120 HI-TEMP
	ADHESIVE AP2400 QUICK SET
	ADHESIVE AP2410 QUICK SET
	PLASTIC AKEMI AP1050
	PLASTIC AKEMI AP1075
	PLASTIC AKEMI AP1200
	PLASTIC AKEMI AP1600
	PLASTIC AKEMI AP2301
	PLASTIC AKEMI AP2307
	PLASTIC AKEMI AP2309
	PLASTIC AKEMI AP2311
	PLASTIC AKEMI AP2316 55/45
	PLASTIC AKEMI FILLER 4
	PLASTIC AKEMI FILLER 7
	PLASTIC AKULON S223G6
	PLASTIC AKULON S223G7
	PLASTIC AKULON S223H2G6
	PLASTIC AP1001-4 FILLER PASTE #4
	PLASTIC AP1001-7 AKEMI FILLER NO 7
	PLASTIC AP1500 SPRAYABLE PRIMAFILL
	PLASTIC AP2206 SURFACE COAT
	PLASTIC AP2209 EPOXY SURFACE COAT
	PLASTIC AP2211 EPOXY SURFACE COAT AND CASTING RESIN
	PLASTIC AP2220 HIGH-TEMP SURFACE EPOXY
	PLASTIC AP2308 EPOXY MASS CASTING
	PLASTIC AP2312 SURFACE CASTING
	PLASTIC AP2316 SURFACE CASTING
	PLASTIC AP2320 HI-TEMP EPOXY CASTING
	PLASTIC AP3030 COLD SOLDER TYPE FILLER PASTE
	PLASTIC AP3031 GLAZING COMPOUND
	PLASTIC TP-901 HARDSET TOOLING PASTE
	PLASTIC TP-903 HARDSET TOOLING PASTE
	PLASTIC TP-906 HARDSET TOOLING PASTE
	PLASTIC TP908 CARVABLE TOOLING PASTE
AKRON CHEMICAL CO	FABRIC CWV2/SOLUBOND 1128
AKZO PLASTICS	PLASTIC AKULON K222D
	PLASTIC AKULON K222F
	PLASTIC AKULON K223B2P1
	PLASTIC AKULON K223HMS6
	PLASTIC AKULON K224G3
	PLASTIC AKULON K224G5
	PLASTIC AKULON K224G6
	PLASTIC AKULON K224G7
	PLASTIC AKULON K224GO
	PLASTIC AKULON K224HM6
	PLASTIC AKULON M223D
	PLASTIC AKULON M231D1
	PLASTIC AKULON M238D1
	PLASTIC AKULON M921D
	PLASTIC AKULON S223D
	PLASTIC AKULON S223E
	PLASTIC AKULON S223F
	PLASTIC AKULON S223G3
	PLASTIC AKULON S223G5
	PLASTIC AKULON S223G6
	PLASTIC AKULON S223GO
	PLASTIC AKULON S223HM6
	PLASTIC AKULON S223HM8
	PLASTIC AKULON S223HMV7
	PLASTIC AKULON S240C
	PLASTIC ARNITEL 40D G1 G6
	PLASTIC ARNITEL 46D G1 G6
	PLASTIC ARNITEL 55D G1 G6
	PLASTIC ARNITEL 74D G1 G6
	PLASTIC ARNITEL EL550
	PLASTIC ARNITEL EL630
	PLASTIC ARNITEL EL740
	PLASTIC ARNITEL EM400
	PLASTIC ARNITEL EM460
	PLASTICS ARNITEL 63D G1-G6
AL-FLA PLACTICS	PLASTIC ACETAL
ALBANY INTERNATIONAL	FABRIC AIRC-S236
	FABRIC COTTON AIRC84410-502/FR
	FABRIC PBI 73300-250 FX BRAID
	FABRIC PBI 84410-426 BRAID
	FABRIC RYTON
	FELT NOMEX/DC92-007 SILICONE COATED
ALICE KING CHATHAM	FABRIC NYLON/COTTON RES JACKET
ALL AMERICAN ENGINEERING CO	WEBBING NYLON NET AAES-236/BG 168
ALL METAL PROCESSING	COATING URETHANE 17875-5008 WHITE
ALL PLASTIC INC	INSULATION FOAM POLYURETHANE FLEXIBLE
ALL SEALS INC	RUBBER SILICONE S571
ALLEGHENY LUDLUM	MAGNET 2V PERMENDUR
ALLEGHENY PLASTICS	SALOX-M
ALLEN INDUSTRIES INC	INSULATION FOAM VONAR CLOTH BACKED TY 3
ALLEN-BRADLEY CO	POTENTIOMETER TYS
ALLEN-BRADLEY CO	PLASTIC ROSITE 3250A
ROSTONE DIV	PLASTIC ROSITE 3250C
	PLASTIC ROSITE 3550A

MSFC-HDBK-527 REV F 9999942 0006843 1

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
ALLEN-BRADLEY CO	PLASTIC ROSITE 3550C
ROSTONE DIV	PLASTIC ROSITE 3550FM
ALLFORCE ACOUSTICS	DAP VINYL/GRAPHITE
	INSULATION FOAM POLYURETHANE FOA-1
	SOUNDSCREEN FOAM/METAL/FOAM
ALLIANCE WEBBING INC	STRAP NEOPRENE/COTTON/RUBBER
ALLIED CHEMICAL	FILM ACLAR 2100
	FILM ACLAR 22A
	FILM ACLAR 33C ECTFE
	FILM ACLAR 33F CTFE
	FILM ACLAR 933A
	FILM CAPRAN 518 GREEN
	FILM CAPRAN 980 NYLON
	FILM CAPRON 80
	HALAR 300 CTFE/ETHYLENE
	HALAR E-CTFE
	MOLD COMPOUND DAP FS5 BLACK 8000
	MOLD COMPOUND DAP FS6 CAF BLUE
	MOLD COMPOUND DAP FS80/GLASS FILLED
	MOLD COMPOUND DIAL 52-01 DAP
	MOLD COMPOUND EPIALL 1288BX
	MOLD COMPOUND EPIALL 1908
	MOLD COMPOUND EPIALL 1914 EPOXY
	MOLD COMPOUND EPIALL 1960 MNRI/EPOX
	MOLD COMPOUND EPIALL S-8723 EPOXY
	MOLD COMPOUND FS10 DAP
	MOLD COMPOUND FS10 DAP TOX RATE STUDY
	PLASTIC AJ50-003
	PLASTIC CAPRON 8200
	PLASTIC CAPRON 8202
	PLASTIC CAPRON 8202C
	PLASTIC CAPRON 8202CL
	PLASTIC CAPRON 8202L
	PLASTIC CAPRON 8203G
	PLASTIC CAPRON 8220HS
	PLASTIC CAPRON 8221HS
	PLASTIC CAPRON 8230G HS
	PLASTIC CAPRON 8231G HS
	PLASTIC CAPRON 8233G HS
	PLASTIC CAPRON 8234G HS
	PLASTIC CAPRON 8253
	PLASTIC CAPRON 8254
	PLASTIC CAPRON 8255
	PLASTIC CAPRON 8259
	PLASTIC CAPRON 8260
	PLASTIC CAPRON 8266G HS
	PLASTIC CAPRON 8270
	PLASTIC CAPRON 8276G HS
	PLASTIC CAPRON 8350
	PLASTIC CAPRON 8360
	PLASTIC HALAR 500
	PLASTIC HALAR 510
	PLASTIC HALAR FLOUROPOLYMER
	PLASTIC HALAR PVF2
	PLASTIC HALON TFE G18
ALLIED CHEMICAL	PLASTIC HALON TFE G700
	PLASTIC HALON TFE G80
	PLASTIC HALON TFE G83
	PLASTIC NYPEL 2314
	PLASTIC NYPEL 2314 FCAT
	PLASTIC NYPEL 2360
	PLASTIC NYPEL 2365G
	PLASTIC NYPEL 6033G
	PLASTIC PAXON 3201
	PLASTIC PAXON 3204
	PLASTIC PAXON 3205
	PLASTIC PAXON 3207
	PLASTIC PAXON 3303
	PLASTIC PAXON 4700
	PLASTIC PAXON AA-50-003
	PLASTIC PAXON AA-50-60
	PLASTIC PAXON AA50-180
	PLASTIC PAXON AA50-250
	PLASTIC PAXON AA55-100
	PLASTIC PAXON AA55-400
	PLASTIC PAXON AA55-60
	PLASTIC PAXON AA55-80
	PLASTIC PAXON AA60-003
	PLASTIC PAXON AA60-007
	PLASTIC PAXON AB40-003
	PLASTIC PAXON AB50-003
	PLASTIC PAXON AB55-003
	PLASTIC PAXON AC40-003
	PLASTIC PAXON AC55-003
	PLASTIC PAXON AE50-003
	PLASTIC PAXON AF40-003
	PLASTIC PAXON AG55-003
	PLASTIC PAXON AK53-004
	PLASTIC PAXON AP60-007
	PLASTIC PAXON BA50-100
	PLASTIC PAXON FP60-018
	PLASTIC PETRA 130 FR
	PLASTIC PETRA 140
	PLASTIC PETRA 149
	PLASTIC PETRA 150
	PLASTIC PETRA 230
	PLASTIC POLYMIST F-5
	PLASTIC POLYMIST F-510
	PLASTIC POLYMIST F-5A
ALLIED FIBERS	FABRIC SPECTRA 900
	PLASTIC CAPRON 8267G
	PLASTIC PAXON AA55-600
	PLASTIC PAXON FD60-018
ALLIED PRODUCTS	ADHESIVE E-SOLDER 3012
	COATING IRIDITE 14-2/CHROMATE
	MOLD COMPOUND MARAGLASS 655/555 EPX
ALLIED RESIN CORP	ADHESIVE QUANTUM 701
	ADHESIVE QUANTUM 702
	ADHESIVE QUANTUM 703

MSFC-HDBK-527 REV F 9999942 0006844 3

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
ALLIED RESINOUS PRODUCTS INC	PLASTIC RESINOL TYPE A
	PLASTIC RESINOL TYPE D
	PLASTIC RESINOL TYPE F
	PLASTIC STYRONOL
ALMAY INC	DEODORANT SOLID UNSCENTED
	EYE PENCIL ALMAY COLOR GENTLE
	MASCARA RICH LASH THICKENING
ALPHA MILLS	FABRIC COTTON 100% COMFORT 3640
	FABRIC POLYESTER/COTTON
	GLOVE COMFORT COTTON/POLYESTER
ALPHA WIRE CORP	LACING TAPE NYLON/DACRON LC136
	TUBING FP301 TYPE 2 POLYOLEFIN HS
	TUBING TEFLON FEP HST
AMATEX	FABRIC NOR-FAB 400/8PT22
	FABRIC THERMOGLASS HEAT TREATED
AMER SMELTING & RF	WAX ETHONE 18
AMERICAN AEROSPACE	COATING SEMIGLOSS ENAMEL ZN/CR04
AMERICAN CHEMICAL	ADHESIVE 810 OIL/GRIP
	ADHESIVE DYMAX 181
	ADHESIVE DYMAX 20017
	ADHESIVE DYMAX 415
	ADHESIVE DYMAX 602
	ADHESIVE DYMAX 628
	ADHESIVE DYMAX 828 OIL/GRIP
	ADHESIVE DYMAX 832 OIL/GRIP
	ADHESIVE DYMAX 845 OIL/GRIP
	ADHESIVE DYMAX 847 OIL/GRIP
	ADHESIVE DYMAX 901
	ADHESIVE DYMAX 902
	ADHESIVE LIGHTWELD 183
	ADHESIVE LIGHTWELD 184
	ADHESIVE LIGHTWELD 185
	ADHESIVE LIGHTWELD 305
	ADHESIVE LIGHTWELD 401
	ADHESIVE LIGHTWELD 432
	ADHESIVE LIGHTWELD 458
	ADHESIVE LIGHTWELD 625
	ADHESIVE LIGHTWELD 911
	ADHESIVE LIGHTWELD 912
	DYMAX 840 OIL/GRIP
	LIGHT-WELD 181/ACRYLIC ADHES
	LIGHT-WELD 182 ACRYLIC ADHES
AMERICAN CLEANING	HOSE NEOPRENE P/N 801005
AMERICAN CYANAMID	ADHESIVE 330U
	ADHESIVE BR624
	ADHESIVE BR626
	ADHESIVE BR662
	ADHESIVE BR92A
	ADHESIVE BR95
	ADHESIVE EPOXY FM300M
	ADHESIVE EPOXY FM73 POLYESTER FILM
	ADHESIVE EPOXY FM73M FILM ON POLYESTER MAT
	ADHESIVE EPOXY PASTE CORFIL 6/5
	ADHESIVE FILM FM1000 POLYAMIDE
	ADHESIVE FILM FM123-2 FILM EPOXY

MANUFACTURER	DESIGNATION
AMERICAN CYANAMID	ADHESIVE FILM FM123-2LVC EPOXY
	ADHESIVE FILM FM123-5
	ADHESIVE FILM FM150-2 LP15
	ADHESIVE FILM FM150-2U
	ADHESIVE FILM FM24 EPOXY
	ADHESIVE FILM FM30
	ADHESIVE FILM FM300 EPOXY
	ADHESIVE FILM FM300K
	ADHESIVE FILM FM32
	ADHESIVE FILM FM33
	ADHESIVE FILM FM34B-18
	ADHESIVE FILM FM34B-184
	ADHESIVE FILM FM36
	ADHESIVE FILM FM40
	ADHESIVE FILM FM400
	ADHESIVE FILM FM400/BR400 WITH ALUMINUM
	ADHESIVE FILM FM404
	ADHESIVE FILM FM43
	ADHESIVE FILM FM96 STRUCTURAL
	ADHESIVE FILM FM96U STRUCTURAL
	ADHESIVE FILM FXM250
	ADHESIVE FM137/BR127
	ADHESIVE FM238/BR238
	ADHESIVE FM330
	ADHESIVE FM350/BR154
	ADHESIVE FM3505/BR154
	ADHESIVE FM53/BR53
	ADHESIVE FM53U/BR53
	ADHESIVE FM61/BR227
	ADHESIVE FM61/BR227A
	ADHESIVE FM73/BR127
	ADHESIVE FM73/BR73
	ADHESIVE FM73M/BR127
	ADHESIVE FOAM FM37 MODIFIED EPOXY
	ADHESIVE FOAM FM41
	ADHESIVE FOAM HT424 T2
	ADHESIVE FXM410
	ADHESIVE HT424 EPOXY
	ADHESIVE HT424 THIXOTROPIC PASTE
	COATING BR 127 EPOXY
	COATING PM47 PRIMER
	FILLER CORFIL 615 EPOXY
	LAMIN CYCOM 6101-2/7781
	MOLD COMPOUND GLASKYD 2051B GL/ALKD
	PLASTIC CYGLAS 508
	PLASTIC CYGLAS 600
	PLASTIC CYGLAS 605
	PLASTIC CYGLAS 610
	PLASTIC CYGLAS 615
	PLASTIC CYGLAS 620
	PLASTIC CYGLAS 620M
	PLASTIC CYGLAS 620X
	PLASTIC GLASKYD 1901
	PLASTIC GLASKYD 1902
	PLASTIC GLASKYD 1910

MSFC-HDBK-527 REV F 9999942 0006845 5

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
AMERICAN CYANAMID	PLASTIC GLASKYD 2201
	PLASTIC GLASKYD 3001H
	PLASTIC GLASKYD 4000
	PLASTIC GLASKYD 4001
	PLASTIC GLASKYD 4002
	RUBBER URETHANE CYANAPRENE 3090
AMERICAN CYANAMID/ LOCKHEED	ADHESIVE FM73M ON GRAPHITE EPOXY PLATES T50/934
AMERICAN DURAFILM	COATING DURAFILM ENAMEL
	TUBING LAMINATED/ROLLED PTFE RESIN/GLASS FABRIC BASE
AMERICAN FELT & FILTER	FELT NOMEX 62HT/14
AMERICAN FINISH & CHEMICAL	ADHESIVE NEOPRENE E2084
AMERICAN GAS & CHEMICAL	COMPOUND LEAK TEST
	COMPOUND LEAK TEST MMSY824C100
	COMPOUND LEAK TEST N727C
	COMPOUND LEAK-TEC 160X
	COMPOUND LEAK-TEC FORMULA #277 NE
AMERICAN HOECHST	PLASTIC HOSTAFLON TF1100
	PLASTIC HOSTAFLON TF1400
	PLASTIC HOSTAFLON TF1620
	PLASTIC HOSTAFLON TF1620F
	PLASTIC HOSTAFLON TF1640
	PLASTIC HOSTAFLON TF1740
	PLASTIC HOSTAFLON TF1760
	PLASTIC HOSTAFLON TF5032
	PLASTIC HOSTAFLON TF5033
	PLASTIC HOSTAFORM C13021
	PLASTIC HOSTAFORM C13031
	PLASTIC HOSTAFORM C2521
	PLASTIC HOSTAFORM C2541
	PLASTIC HOSTAFORM C27021
	PLASTIC HOSTAFORM C32021
	PLASTIC HOSTAFORM C32021AST
	PLASTIC HOSTAFORM C52021
	PLASTIC HOSTAFORM C9021
	PLASTIC HOSTAFORM C9021GV
	PLASTIC HOSTAFORM C9021K
	PLASTIC HOSTAFORM C9021M
	PLASTIC HOSTAFORM C9021TF
	PLASTIC HOSTAFORM S27063
	PLASTIC HOSTAFORM S27064
	PLASTIC HOSTAFORM S27073
	PLASTIC HOSTAFORM S27076
	PLASTIC HOSTAFORM S9063
	PLASTIC HOSTAFORM S9064
	PLASTIC HOSTAFORM T1020
	PLASTIC HOSTALEN GA7260
	PLASTIC HOSTALEN GB6450
	PLASTIC HOSTALEN GC7260
	PLASTIC HOSTALEN GD4760
	PLASTIC HOSTALEN GD6250
	PLASTIC HOSTALEN GD7255
	PLASTIC HOSTALEN GF4750
AMERICAN HOECHST	PLASTIC HOSTALEN GF4760
	PLASTIC HOSTALEN GF7740F
	PLASTIC HOSTALEN GF7740F2
	PLASTIC HOSTALEN GF7750M
	PLASTIC HOSTALEN GF9360K
	PLASTIC HOSTALEN GH4765
	PLASTIC HOSTALEN GM5010T2
	PLASTIC HOSTALEN GM5040
	PLASTIC HOSTALEN GM5040T12
	PLASTIC HOSTALEN GM5040T50
	PLASTIC HOSTALEN GM5050
	PLASTIC HOSTALEN GM6255
	PLASTIC HOSTALEN GM7040G
	PLASTIC HOSTALEN GM7255
	PLASTIC HOSTALEN GM7745
	PLASTIC HOSTALEN GM7746
	PLASTIC HOSTALEN GM8255
	PLASTIC HOSTALEN GM9050F
	PLASTIC HOSTALEN GM9240HT
	PLASTIC HOSTALEN GM9255F
	PLASTIC HOSTALEN GM9350C
	PLASTIC HOSTALEN GR7255P
	PLASTIC HOSTALEN GUR
	TEFLON TFE VIRGIN
AMERICAN MARKETING	TUBING PTFE SHRINKABLE
AMERICAN METASEAL CO	SEALANT METASEAL 19V5M POLYESTER
AMERICAN OIL & SUPPLY	COMPOUND PQ HEAT SINK
AMERICAN OPTICAL	ANTI-FOG SOLUTION P/N 350AF
	GOGGLES SUN 8465-530-4083
	PLASTIC LEXAN 9034-112/A4T COATING OVER DC Q9-6312
	SUNGLASSES AND CASE
AMERICAN ROBIN	FASTENER POLYESTER SLIDE 321
AMERICAN RUBBER CO	RUBBER SILICONE 4216A
AMERICAN SCIENTIFIC	INSULATION FOAM TEST TUBE RACK 2610
	RUBBER BUTYL B7764-11
AMERICAN VELODUR INC	ADHESIVE VELODUR METAL/EPOXY
AMERICAN WESTERN	INSULATION FOAM POLYURETHANE AW420
AMERICAN WHITE CROSS LABS	BANDAGE MOLESKIN
	FABRIC MOLESKIN
AMERON	COATING DIMETCOTE #6
	COATING DIMETCOTE 3/AMERCOTE 383HS
AMES METAL	CAN RODENT
AMETEK	COATING PRIMER TFE TEST DISCS
	RUBBER VITON A
	RUBBER VITON FLUID RESISTANT
	TEFLON TFE VIRGIN
	TEFLON TFE/25% GLASS
	TUBING PTFE HST
	WIRE ELEC TEFLON TFE
AMI INDUSTRIES	CUSHION SEAT CREW WITH PASSENGER
	WEBBING MURDOCK X854 POLYESTER
AMICON	ADHESIVE AMICON 845 EPOXY
	ADHESIVE AMICON A329-1
	ADHESIVE AMICON C110

MSFC-HDBK-527 REV F 9999942 0006846 7

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
AMICON	ADHESIVE AMICON C115
	ADHESIVE AMICON C120
	ADHESIVE AMICON C770-4
	ADHESIVE AMICON C770-5
	ADHESIVE AMICON C805
	ADHESIVE AMICON C840
	ADHESIVE AMICON C840-23 EPOXY
	ADHESIVE AMICON C850-16
	ADHESIVE AMICON C850-5
	ADHESIVE AMICON C850-5A
	ADHESIVE AMICON C850-6
	ADHESIVE AMICON C868-1
	ADHESIVE AMICON C928-46
	ADHESIVE AMICON C929-72-9
	ADHESIVE AMICON C930-55-2
	ADHESIVE AMICON C932-46
	ADHESIVE AMICON C932-62-1
	ADHESIVE AMICON C940-7
	ADHESIVE AMICON CS489
	ADHESIVE AMICON CS489-2
	ADHESIVE AMICON G843
	ADHESIVE AMICON ME5146
	ADHESIVE AMICON ME778-6
	ADHESIVE AMICON ME785
	ADHESIVE AMICON ME845-3
	ADHESIVE AMICON ME855-2
	ADHESIVE AMICON ME865-1
	ADHESIVE AMICON ME868-2
	ADHESIVE AMICON ME930-12-4
	ADHESIVE AMICON ME932-44
	ADHESIVE AMICON SC110
	ADHESIVE AMICON SC130
	ADHESIVE AMICON SC130-3
	ADHESIVE AMICON SC17
	ADHESIVE AMICON SLC C860-2
	ADHESIVE AMICON T1206
	ADHESIVE AMICON T426
	ADHESIVE AMICON TG86
	ADHESIVE AMICON TG86EC
	ADHESIVE AMICON TG86TC
	ADHESIVE AMICON XT1369 A/B
	ADHESIVE UNISET 108B
	ADHESIVE UNISET 3663
	ADHESIVE UNISET 927-10
	ADHESIVE UNISET A304-6
	ADHESIVE UNISET A312
	ADHESIVE UNISET A316-34
	ADHESIVE UNISET A316-4 EPOXY
	ADHESIVE UNISET A359-4 EPOXY
	ADHESIVE UNISET A410-10
	ADHESIVE UNISET A451 EPOXY
	ADHESIVE UNISET D271 EPOXY
	ADHESIVE UNISET D272
	ADHESIVE UNISET D275
	ADHESIVE UNISET D275-5

MANUFACTURER	DESIGNATION
AMICON	ADHESIVE UNISET D276
	ADHESIVE UNISET D778
	ADHESIVE UNISET D969
	ADHESIVE UNISET E131
	ADHESIVE UNISET E151-3
	ADHESIVE UNISET E154
	ADHESIVE UNISET E565
	ADHESIVE UNISET G500
	ADHESIVE UNISET G508
	ADHESIVE UNISET G508-1
	ADHESIVE UNISET G582
	ADHESIVE UNISET G583
	ADHESIVE UNISET G757-1
	ADHESIVE UNISET G804-3
	ADHESIVE UNISET G843
	ADHESIVE UNISET SE613
	ADHESIVE UNISET SE615
	ADHESIVE UNISET SE616
	ADHESIVE UNISET SE617
	ADHESIVE UNISET SE628
	ADHESIVE UNISET SE629
	ADHESIVE UNISET SE630
	ADHESIVE UNISET SE906-21
	ADHESIVE UNISET T1207
	ADHESIVE UNISET T1316
	ADHESIVE UNISET T219
	ADHESIVE UNISET T4009
	ADHESIVE UNISET T530
	ADHESIVE UNISET T597
	ADHESIVE UNISET T661
	ADHESIVE UNISET T665
	ADHESIVE UNISET T920-2
	ADHESIVE UNISET X2551
	ADHESIVE UNISET XT116-1 WITH B71
	ADHESIVE UNISET XT1203-4 WITH B71
	ADHESIVE UNISET XT2526
	ADHESIVE UNISET XT4064-3 WITH B100
	ADHESIVE UNISET XT5012
	ADHESIVE UNISET XT5066
	ADHESIVE UV990-24-11
	ADHESIVE XLC C860-1
	ADHESIVE XLC C940-2
	ADHESIVE XLC C940-4
	ADHESIVE XT5235
	COATING UNICOAT 2081-31A EPOXY
	COATING UNICOAT 501
	COMPOUND UNISET A316-7 EPOXY
AMOCO	LAMIN THORNEL P75 2K/ERLX 1962 QUASI ISOTROPIC LAYUP
	LAMIN THORNEL P75 2K/ERLX 1962 UNIDIRECTIONAL POLYMERIC RESIN/CARBON
	LUBE GREASE AMDEX 2EP
	LUBE GREASE RYKON PREMIUM 2EP
	LUBE GREASE SUPERMIL ASU31052
	PLASTIC 24082

MSFC-HDBK-527 REV F 9999942 0006847 9

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
AMOCO	PLASTIC 260B1
	PLASTIC 290B1
	PLASTIC 3150B
	PLASTIC 3250B
	PLASTIC 3420B
	PLASTIC 3550B
	PLASTIC 360B1
	PLASTIC 403L3
	PLASTIC 404F3
	PLASTIC 408F3
	PLASTIC 4140B
	PLASTIC AMOCO CRYSTAL POLYSTYRENE G1
	PLASTIC AMOCO CRYSTAL POLYSTYRENE G18
	PLASTIC AMOCO CRYSTAL POLYSTYRENE G2
	PLASTIC AMOCO CRYSTAL POLYSTYRENE G3
	PLASTIC AMOCO CRYSTAL POLYSTYRENE R1
	PLASTIC AMOCO CRYSTAL POLYSTYRENE R2
	PLASTIC AMOCO CRYSTAL POLYSTYRENE R3
	PLASTIC AMOCO CRYSTAL POLYSTYRENE R5
	PLASTIC AMOCO CRYSTAL POLYSTYRENE R7
	PLASTIC AMOCO IMPACT POLYSTYRENE H2R
	PLASTIC AMOCO IMPACT POLYSTYRENE H3E
	PLASTIC AMOCO IMPACT POLYSTYRENE H4E
	PLASTIC AMOCO IMPACT POLYSTYRENE H4R
	PLASTIC AMOCO IMPACT POLYSTYRENE HXM
	PLASTIC AMOCO IMPACT POLYSTYRENE M9
	PLASTIC AMOCO IMPACT POLYSTYRENE M9R
	PLASTIC AMOCO POLYPROPYLENE 4017
	PLASTIC AMOCO POLYPROPYLENE 4018
	PLASTIC AMOCO POLYPROPYLENE 4036
	PLASTIC AMOCO POLYPROPYLENE 4039
	PLASTIC AMOCO POLYPROPYLENE 4046
	PLASTIC AMOCO POLYPROPYLENE 4222
	PLASTIC AMOCO POLYPROPYLENE 4228
	PLASTIC AMOCO POLYPROPYLENE 5219
	PLASTIC AMOCO POLYPROPYLENE 7232
	PLASTIC AMOCO POLYPROPYLENE 7234
	PLASTIC AMOCO POLYPROPYLENE CR22 NA
	PLASTIC AMOCO POLYPROPYLENE CR35 A
	PLASTIC AMOCO POLYPROPYLENE CR35 NA
	PLASTIC TORLON 4203
	PLASTIC TORLON 4301 POLYIMIDE-AMIDE
AMP INC	CONNECTOR ELECTRICAL
	CONNECTOR ELECTRICAL 22541
	CONNECTOR THERMAL PLASTIC
	KEL-F CTFE UNPLASTICIZED
	PLASTIC CELANEX 3310
ANCHOR PACKING CO	RUBBER VITON FLUID RESISTANT
ANDREW BROWN	COATING A136 EPOXY
	COATING A423/T252 EPOXY
	COATING ENAMEL HS767/EPX HS768 A1
	COATING L496A-66/37038 CAM LACQURE
	COATING ZINC CHROMATE
ANTIFLASH CORP	FABRIC P101VIP
	FABRIC P310 ULTRA

MANUFACTURER	DESIGNATION
ANTIFLASH CORP	FABRIC P313
	FABRIC VIP INTERLOCK KNIT
ANTON MAIX FABRICS INC	FABRIC DISCOVERY 86U101-5 OI LAVENDER BLUE 80% WORSTED WOOL 20% RAYON
	FABRIC X-OGEN CAVALRY TWILL LAVANDER 85% WOOL/15% KEVLAR
	FABRIC X-OGEN WOOL CORD #20 PETROL 80% WORSTED WOOL 20% KEVLAR CARBON
ANVET ELECTRONICS	CONNECTOR MS2743E14F37PC
APEX	BOX APEX TAPE
	MULTI-LAYERED INSULATION AL/KAPTON/DACRON/NOMEX/MYLAR
	PLASTIC APEX 1001
	PLASTIC APEX 1002
	PLASTIC APEX 1003
	PLASTIC APEX 1004
	PLASTIC APEX 1007
	PLASTIC APEX 1008
	PLASTIC APEX 1009
	PLASTIC APEX 1011
	PLASTIC APEX 1013
	PLASTIC APEX 1015
	PLASTIC APEX 1216
	PLASTIC APEX 1217
	PLASTIC APEX 1221
	PLASTIC APEX 1369
	PLASTIC APEX 1464
	PLASTIC APEX 1521
	PLASTIC APEX 1522
	PLASTIC APEX 1523
	PLASTIC APEX 1524
	PLASTIC APEX 1525
	PLASTIC APEX 1526
	PLASTIC APEX 1527
	PLASTIC APEX 1560
	PLASTIC APEX 1561
	PLASTIC APEX 1562
	PLASTIC APEX 1563
	PLASTIC APEX 1564
	PLASTIC APEX 1565
	PLASTIC APEX 1566
	PLASTIC APEX 1581
	PLASTIC APEX 1582
	PLASTIC APEX 1583
	PLASTIC APEX 1584
	PLASTIC APEX 1585
	PLASTIC APEX 1586
	PLASTIC APEX 1587
	PLASTIC APEX 1589
	PLASTIC APEX 1590
	PLASTIC APEX 1835
	PLASTIC APEX 1850
	PLASTIC APEX 1877
	PLASTIC APEX 370
	PLASTIC APEX 4101

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
APEX	PLASTIC APEX 4103
	PLASTIC APEX 4109
	PLASTIC APEX 4217
	PLASTIC APEX 776
	RUBBER TELCAR 101
	RUBBER TELCAR 102
	RUBBER TELCAR 150
	RUBBER TELCAR 301
	RUBBER TELCAR 302
	RUBBER TELCAR 310
	RUBBER TELCAR 312
	RUBBER TELCAR 332
	RUBBER TELCAR 340
	RUBBER TELCAR 340E
	RUBBER TELCAR 340S
	RUBBER TELCAR 355
APLIX	FASTENER APLIX 810 POLYESTER HOOK
	FASTENER APLIX 810 POLYESTER LOOP
	FASTENER APLIX 820 NOMEX NON-MELTING HOOK
	FASTENER APLIX 820 NOMEX NON-MELTING HOOK AND LOOP
	FASTENER APLIX 820 NOMEX NON-MELTING LOOP
APPLE RUBBER INC	RUBBER NEOPRENE CR70
APPLETON	COATING INK 002-0001-01 STAMP
APPLIED COMPOSITES	PLASTIC 8007
	PLASTIC 8016
	PLASTIC 8020
	PLASTIC 8022
	PLASTIC 8031
	PLASTIC 8038
	PLASTIC 8041
	PLASTIC 8049
	PLASTIC 8050
	PLASTIC 8057
	PLASTIC 8061
	PLASTIC 8068
	PLASTIC 8072
	PLASTIC 8079
	PLASTIC 8085
	PLASTIC 8086
	PLASTIC 8659
APPLIED PLASTICS	ADHESIVE CERAMIC APCO R310 EPOXY
	ADHESIVE EPOXY P460
	ADHESIVE R393
	LAMIN SAFE-T-POXY
	PLASTIC 2401/2180
	PLASTIC 2403 A/B
	PLASTIC 2405/2140
	PLASTIC 2410/2183
	PLASTIC 2411/2311
	PLASTIC 2414/2180
	PLASTIC 2414/2320
	PLASTIC 2415/2180
	PLASTIC 2417/2180
	PLASTIC 2418/2140

MANUFACTURER	DESIGNATION
APPLIED PLASTICS	PLASTIC 2421/2140
	PLASTIC 2422/2140
	PLASTIC 2424/2174
	PLASTIC 2425/2305
	PLASTIC 2425/2310
	PLASTIC 2425/2324
	PLASTIC 2428/2330
	PLASTIC 2434/2310
	PLASTIC 2434/2320
	PLASTIC 2434/2323
	PLASTIC 2434/2330
	PLASTIC 2438/2180
	PLASTIC 2441/2180
	PLASTIC 2481/2161
	PLASTIC 2482/2192
	PLASTIC 2484/2192
	PLASTIC 2493/2164
	PLASTIC 5323 A/B
	PLASTIC APCO 1475
	PLASTIC APCO 5290
	PLASTIC APCO 5293
	PLASTIC APCO 5303
	PLASTIC APCO 5313
	PLASTIC APCO 5314
	PLASTIC APCO 5321
	PLASTIC APCO 5323
	PLASTIC APCO 5363
	PLASTIC APCO 5393
	PLASTIC APCO 5823
APPLIED RESEARCH LAB	COATING CONVERSION CHROMATE
	COATING PRIMER CONVERSION CHROMATE
APPLIED RUBBER	RUBBER VITON A
	RUBBER VITON B50
	RUBBER VITON E60C
AQM	ABLATIVE COMPOUND PHENOLIC/SILICONE
	ABLATIVE MA255 T1
	ACID LAURIC
	CABLE SPLICE NAS1744
	CARBON BLACK
	CETYL ALCOHOL-FASTENR LUB ONLY
	CLAMP 45L83 LOOP WITH SILICONE CUSHION
	CLAMP CUSHION TEFLON (13K)
	COATING ALKYD GLOSS ENAMEL YELLOW
	COATING CORROSION PREVENTIVE
	COATING ENAMEL LUSTERLESS STYRENE ALKYD
	COATING ENAMEL YELLOW
	COATING LACQUER PAINT QUICK DRY
	COATING POLYAMIDE RED 11136 EPOXY
	COATING POLYIMIDE BLACK 37038 EPOXY
	CONNECTOR ELECTRICAL
	DUCT SILICONE/HT6 NOMEX
	DYE RED
	FABRIC FIBERGLASS/CHLOROPRENE
	FELT WOOL
	GLOVE VINYL DERMA THIN

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006849 2

MANUFACTURER	DESIGNATION
AQM	INK MARKING STENCIL
	INK NOC
	INSULATION PAPER ARMITE SLOT
	INSULATION WIRE CU/TFE/GL
	IRON OXIDE (INORGANIC)
	KEL-F CTFE UNPLASTICIZED
	LACQUER ACRYLIC NITROCEL 17038
	LACQUER CELLULOSE NITRATE BLAK
	LACQUER CELLULOSE NITRATE YELLOW
	LACQUER GREEN COLOR 11105
	LACQUER YELLOW
	LAMIN PHENOLIC/GLASS
	LEATHER GOATSKIN
	LUBE DRY FILM
	LUBE OIL PRESERVATIVE
	MOLD COMPOUND TFE/GLASS/MOS2
	PAPER FILTER
	PARAFFIN WAX
	PLATE TERMINAL POLYESTER
	POLYETHYLENE
	PROPELLANT BSM U7P19048
	PROPELLANT LINER BSM U7L004B
	RUBBER BUTYL R/S 201-6
	RUBBER EPR NOC
	RUBBER FLUOROSILICONE
	RUBBER NEOPRENE
	RUBBER NITRILE
	RUBBER SILICONE CL 2A & 2B GR 70
	SEALANT THREAD LOCKING COMPOUND
	SILICA FUSED INORGANIC
	TAPE GLASS/THERMOSET PS
	TAPE PAPER DOUBLEFACE PSA
	TEFLON TFE RED STRIPED
	TEFLON TFE VIRGIN
	TUBING FIBERGLASS
	TUBING PLASTIC REINFORCED/CLEAR
	TUBING POLYESTER HST
	WALLBOARD/PASTE/SEAMING TAPE
	WALLBOARD/PASTE/TAPE COATED
	WEBBING NMX/HOOK HAQ-12-1-100
	WEBBING NYLON
	WEBBING NYLON FIRE/WATER PROOF
	WEBBING NYLON/VELCRO/NOMEX/METALIZED
	UTILITY STRAP
	WEBBING STRAP NYLON FIRE/WATERPROOF
	WIRE ELEC FEP WITH POLYIMIDE TAPE
	WIRE ELEC FEP/POLYIMIDE TAPE
	WIRE ELEC KYNAR PVF
	WIRE ELEC MAGNET CL200 TYPE K POLYESTER
	WIRE ELEC MAGNET POLYESTER-IMIDE OR POLYESTER-AMIDE-IMIDE CL 180 TYPE H
	WIRE ELEC TEFLON TFE
	WIRE ELEC THERMOCOUPLE FIBERGLASS
	WIRE ELEC WRAPPED IN P2650 SILICONE TAPE
AQM	WIRE MAGNET RECTANGULAR POLYVINYL FORMAL COATED CLASS 105 TYPE 2 AND 4
	WOOD SOFT COMMERCIAL
ARAN DEE ASSOCIATES	ADHESIVE RAPIDSET BLUE EPOXY
ARBROOK INC	POWDER BIOSORB B210
ARC	LAMIN EPOXY/GLASS CE9010A/7781
ARCAL CHEMICALS	POTTING COMPOUND ARCOSET 200 EPOXY
ARCO CHEMICAL CO	PLASTIC ARLOY 1000
	PLASTIC ARLOY 1100
	PLASTIC ARLOY 1200
	PLASTIC ARLOY 2000
	PLASTIC DYLARK 132
	PLASTIC DYLARK 138
	PLASTIC DYLARK 232
	PLASTIC DYLARK 238
	PLASTIC DYLARK 238 F20A
	PLASTIC DYLARK 238S
	PLASTIC DYLARK 238S F20A
	PLASTIC DYLARK 240
	PLASTIC DYLARK 250
	PLASTIC DYLARK 332
	PLASTIC DYLARK 338
	PLASTIC DYLARK 338S
	PLASTIC DYLARK 338S F20A
	PLASTIC DYLARK 350
	PLASTIC DYLARK 378
	PLASTIC DYLARK 700
ARDE	COATING POLANE TOPCOAT/KEVLAR
AREMCO PRODUCTS	ADHESIVE AREMCOBOND 515
	ADHESIVE AREMCOBOND 517 EPOXY
	ADHESIVE AREMCOBOND 525
	ADHESIVE AREMCOBOND 526
	ADHESIVE AREMCOBOND 529
	ADHESIVE AREMCOBOND 556
	ADHESIVE AREMCOBOND 561
	ADHESIVE AREMCOBOND 568
	ADHESIVE AREMCOBOND 570
	ADHESIVE CERAMABOND 552
	ADHESIVE CERAMABOND 569
	ADHESIVE CERAMABOND 618
	ADHESIVE CERAMIC ULTRATEMP 516
	ADHESIVE CRYSTALBOND 509 TEMPORARY WASH-AWAY
	ADHESIVE CRYSTALBOND 555 TEMPORARY WASH-AWAY
	ADHESIVE CRYSTALBOND 590 TEMPORARY WASH-AWAY
	ADHESIVE GRAPHIBOND 551A
	ADHESIVE GRAPHIBOND 551R
	ADHESIVE PYROBOND 566
	ADHESIVE PYROPUTTY 600
	COATING PYROCOAT 565 (INORGANIC)
	PLASTIC EZ-CAST 521 PLASTIC MOLDING COMPOUND

MSFC-HDBK-527 REV F 9999942 0006850 9

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
AREMCO PRODUCTS	PLASTIC EZ-CAST 588 PLASTIC MOLDING COMPOUND
ARI INDUSTRIES	SEALANT AIR-O-SEAL
ARIZONA CHEMICAL	PLASTIC ZONAREZ 7115
	PLASTIC ZONAREZ 7115 LITE
	PLASTIC ZONAREZ 7125
	PLASTIC ZONAREZ 7125 LITE
	PLASTIC ZONAREZ ALPHA 25
	PLASTIC ZONAREZ B-125
	PLASTIC ZONAREZ M115
	PLASTIC ZONAREZA B-115
	PLASTIC ZONATAC 105
	PLASTIC ZONATAC 105 LITE
	PLASTIC ZONATAC 115 LITE
	PLASTIC ZONATAC 501
	PLASTIC ZONATAC 501 LITE
	PLASTIC ZONESTER 100
	PLASTIC ZONESTER 55
	PLASTIC ZONESTER 65
	PLASTIC ZONESTER 75
	PLASTIC ZONESTER 85
ARMCO INC	FABRIC FIBERGLASS/VITON 5707
ARMEL ELECTRONICS	CONNECTOR PC BOARD DAP/ORLON
ARMITE LABS	SEALANT LOX-SAFE
ARMSTRONG	ADHESIVE ARMAFLEX BLACK
	ADHESIVE ARMSTRONG 520 NEOPRENE
	ADHESIVE ARMSTRONG 529
	ADHESIVE ARMSTRONG A12 EPOXY
	ADHESIVE ARMSTRONG A12-2
	ADHESIVE ARMSTRONG A12-3
	ADHESIVE ARMSTRONG A12/T
	ADHESIVE ARMSTRONG A18 EPOXY PASTE
	ADHESIVE ARMSTRONG A2/A
	ADHESIVE ARMSTRONG A2/E
	ADHESIVE ARMSTRONG A2/H20
	ADHESIVE ARMSTRONG A2/W
	ADHESIVE ARMSTRONG A271
	ADHESIVE ARMSTRONG A3
	ADHESIVE ARMSTRONG A3/A
	ADHESIVE ARMSTRONG A3/E
	ADHESIVE ARMSTRONG A31
	ADHESIVE ARMSTRONG A36
	ADHESIVE ARMSTRONG A39
	ADHESIVE ARMSTRONG A40
	ADHESIVE ARMSTRONG A5-4318/H3486 EPOXY
	ADHESIVE ARMSTRONG A6/A
	ADHESIVE ARMSTRONG A6/E
	ADHESIVE ARMSTRONG A6/H20
	ADHESIVE ARMSTRONG A66
	ADHESIVE ARMSTRONG A7-4322
	ADHESIVE ARMSTRONG A701 EPOXY
	ADHESIVE ARMSTRONG A702
	ADHESIVE ARMSTRONG A706
	ADHESIVE ARMSTRONG A708
	ADHESIVE ARMSTRONG A8-4219/H2-3404 EPOXY
ARMSTRONG	ADHESIVE ARMSTRONG A875 NITRILE RUBBER
	ADHESIVE ARMSTRONG ACTA 1 RESIN
	ADHESIVE ARMSTRONG C1 EPOXY
	ADHESIVE ARMSTRONG C1/A
	ADHESIVE ARMSTRONG C1/E
	ADHESIVE ARMSTRONG C2/A EPOXY
	ADHESIVE ARMSTRONG C3/A
	ADHESIVE ARMSTRONG C3/E
	ADHESIVE ARMSTRONG C4/D
	ADHESIVE ARMSTRONG C4/W
	ADHESIVE ARMSTRONG C7/H20
	ADHESIVE ARMSTRONG C7/W EPOXY
	ADHESIVE ARMSTRONG C7/W1
	ADHESIVE ARMSTRONG C7/W2
	ADHESIVE ARMSTRONG C7/W3
	ADHESIVE ARMSTRONG D218 INDUSTRIAL
	ADHESIVE ARMSTRONG D222 INDUSTRIAL
	ADHESIVE ARMSTRONG D234 CONTACT
	ADHESIVE ARMSTRONG D283 INDUSTRIAL
	ADHESIVE ARMSTRONG D284
	ADHESIVE ARMSTRONG D500 CONTACT
	ADHESIVE ARMSTRONG F1450 PANEL AND WALLBOARD
	ADHESIVE ARMSTRONG J1162 RESIN BASED
	ADHESIVE ARMSTRONG J1177 GREY
	ADHESIVE ARMSTRONG J1188 INDUSTRIAL
	ADHESIVE ARMSTRONG J1199 TP INDUSTRIAL PART A
	ADHESIVE ARMSTRONG J1199 TP INDUSTRIAL PART B
	ADHESIVE ARMSTRONG N111 INDUSTRIAL
	ADHESIVE ARMSTRONG N117 INDUSTRIAL
	ADHESIVE ARMSTRONG N122
	ADHESIVE ARMSTRONG S1200 CONTACT
	ADHESIVE ARMSTRONG S139 TILE-ON
	ADHESIVE ARMSTRONG S140 GLAZECRAFT WALLTILE
	ADHESIVE ARMSTRONG S200 A/B
	ADHESIVE ARMSTRONG S235 MULTIPURPOSE
	ADHESIVE ARMSTRONG S252 PAVIMAR
	ADHESIVE ARMSTRONG S280
	ADHESIVE ARMSTRONG S285 WALLBASE
	ADHESIVE ARMSTRONG S553 SEAMSEALING
	ADHESIVE ARMSTRONG S580
	ADHESIVE ARMSTRONG S665 TROWELABLE INTERFLEX
	ADHESIVE ARMSTRONG S670 LATEX INTERFLEX
	ADHESIVE ARMSTRONG S700 TILE BRUSH-ON
	ADHESIVE ARMSTRONG S750 TILE ROLL-ON
	ADHESIVE ARMSTRONG S821 SEAMSEALING
	ADHESIVE ARMSTRONG S89 TILE
	ADHESIVE ARMSTRONG S90 TILE
	ADHESIVE ARMSTRONG X81/A EPOXY
	ADHESIVE ARMSTRONG X81/E
	COATING ARMAFLEX VINYL

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
ARMSTRONG	COATING E318315H FUSE EPOXY
	COATING E393025N BLACK EPOXY
	COATING E85552 RESIN WHITE EPOXY
	COATING FUSECOTE/A34 EPOXY
	COATING X300 EPOXY
	INSULATION ARMAFLEX (FR) NEOPRENE
	INSULATION ARMAFLEX RUBBER
	INSULATION ARMAFLEX/ARMSTRONG 520
	INSULATION CORK
	INSULATION FOAM ARMAFLEX
	INSULATION PIPE ARMAFLEX AP
	RUBBER SPONGE NEOPRENE
	TAPE ARMAFLEX LA3500 10-67 PS
ARMSTRONG CORK	CORK COMPOUND K5NA
ARNO PRODUCTS	TAPE FABRIC C516 VINYL COATED
	TAPE PS C706 BLUE
ARROW ADHESIVES CO	ADHESIVE 80X12
	ADHESIVE AA1104
	ADHESIVE AA1104MB
	ADHESIVE AA1104RB
	ADHESIVE AA1106
	ADHESIVE AA1108
	ADHESIVE AA1116
	ADHESIVE AA1120
	ADHESIVE AA1122
	ADHESIVE AA1124
	ADHESIVE AA1128
	ADHESIVE AA1130
	ADHESIVE AA1212
	ADHESIVE AA1604
	ADHESIVE AA1612
	ADHESIVE AA1618
	ADHESIVE AA2304
	ADHESIVE CPVC CEMENT AA1106HB
ARROW SHIRT CO	FABRIC SHIRT JOE NAMATH
ARROWHEAD PRODUCTS	DUCT RUBBER
	FABRIC GLASS/SILICONE AP2363
	FABRIC KEVLAR 49 T120/SILICONE 7021G
	FABRIC NOMEX 2002/FLUOROSILICONE
	FABRIC SILICONE 7243G1523
	FABRIC SILICONE/ARAMID7311NHT6
	FABRIC SILICONE/ARMID 7311K120
	GASKET MATERIAL X106 NOMEX/RUBBER
	GASKET SILICONE 7241/KEVLAR K120
	INSULATION FOAM URETHANE/LT80/REFSET
	COATED
	LAMIN EPOXY AP3012A
	LAMIN/EPOXY/EPOCAST 1468/FYROL FR2
	RUBBER BUTYL
	RUBBER EPR AP3013
	RUBBER SILICONE AP3004 CL 3A GR 50
	SEALANT VITON AP2709
ARTUS CORP	CELLULOSE ACETATE
ASAHI GLASS CO	CLAMP HIGH THERMAL KCA-44
ASHAWAY LINE & TWINE	CORD KEVLAR 29 73457

MANUFACTURER	DESIGNATION
ASHLAND CHEM	ADHESIVE AROPOL 7240
	ADHESIVE AROSET 1044Z40
	ADHESIVE AROSET 1051Z45
	ADHESIVE AROSET 1081Z45
	ADHESIVE AROSET 1214C30
	ADHESIVE AROSET 1612Z35
	ADHESIVE AROSET 1832Z1-35
	ADHESIVE AROSET 1857Z34
	ADHESIVE AROSET 1910TH52
	ADHESIVE AROSET 2020W50
	ADHESIVE AROSET 2022W50
	ADHESIVE AROSET 2201W50
	ADHESIVE AROSET 2202W50
	ADHESIVE AROSET 2301W50
	ADHESIVE AROSET 2302W50
	ADHESIVE AROSET 2431W50
	ADHESIVE AROSET 2510W62
	ADHESIVE AROSET 2520W60
	ADHESIVE AROSET 2532W50
	ADHESIVE HETRON 700
	ADHESIVE HETRON 800
	ADHESIVE ISOSET WD2A312
	ADHESIVE ISOSET WD3A320
	ADHESIVE PLIOGRIP 6000
	ADHESIVE PLIOGRIP 6600
	ADHESIVE PLIOGRIP 6627
	ADHESIVE PLIOGRIP 6800
	ALCOHOL CETYL ADOL 52NF
	PLASTIC ATLAS POLYETHYLENE (LINEAR)
	PLASTIC ATLAS POLYPROPYLENE HOMOPOLYMER
	PLASTIC ATLAS POLYPROPYLENE V0 HOMOPOLYMER
	PLASTIC ATLAS POLYPROPYLENE V2 HOMOPOLYMER
	PLASTIC ATLAS PVC T2
	PLASTIC ATLASTAFLEX PVC SHEET MEMBRANE
	PLASTIC POLYETHYLENE (LINEAR)
	PLASTIC POLYPROPYLENE HOMOPOLYMER
	PLASTIC POLYPROPYLENE HOMOPOLYMER V-2
	PLASTIC POLYPROPYLENE HOMOPOLYMER V-0
ASHLEY POLYMERS INC	PLASTIC ASHLENE 520
	PLASTIC ASHLENE 521
	PLASTIC ASHLENE 522
	PLASTIC ASHLENE 525LD
	PLASTIC ASHLENE 525LD 13G
	PLASTIC ASHLENE 527LD
	PLASTIC ASHLENE 528BR WO
	PLASTIC ASHLENE 528L 13G
	PLASTIC ASHLENE 528L 25G
	PLASTIC ASHLENE 528L 33G
	PLASTIC ASHLENE 528LW
	PLASTIC ASHLENE 528MS
	PLASTIC ASHLENE 538
	PLASTIC ASHLENE 541
	PLASTIC ASHLENE 630
	PLASTIC ASHLENE 734D
	PLASTIC ASHLENE 735D

MSFC-HDBK-527 REV F 9999942 0006852 2

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
ASHLEY POLYMERS INC	PLASTIC ASHLENE 737
	PLASTIC ASHLENE 738D
	PLASTIC ASHLENE 741
	PLASTIC ASHLENE 830L
	PLASTIC ASHLENE 830L 13G
	PLASTIC ASHLENE 830L 33G
	PLASTIC ASHLENE 830LN
	PLASTIC ASHLENE 840
ASSOCIATED ALLIED	ADHESIVE PLASTOMERIC SEALANT
ASTRO MET	AMCERMET 701-N65
ASTROCOM	CABLE MICROPHONE
ATAN	BAG CAMERA
ATCO	FOOD RAT/MOUSE
ATLANTIC LAMINATES	LAMIN POLYIMIDE/GLASS
ATLAS CORP	ADHESIVE EPOXYBOND PUTTY
	BRAID NOMEX COVER/HARNESS
	HOSE LINER PTFE
	HOSE LINER TEFLON CONDUCTIVE
	HOSE TFE/CARBON FILLED
ATMOSPHERIC SERVICES	COATING ALKYD-MELAMINE ENAMEL
ATOCHEM	PLASTIC FORAFLON 1000HD
	PLASTIC GSMRO2
	PLASTIC NYLON 12 MOLDING GRADE AZMO30
	PLASTIC ORGAMIDE RMNO P40 CD
	PLASTIC ORGAMIDE RMNOCD
	PLASTIC ORGAMIDE RZM 30
	PLASTIC ORGAMIDE RZM15
	PLASTIC ORGATER TMNO
	PLASTIC ORGATER TZM 20
	PLASTIC ORGATER TZM 30 W8
	PLASTIC PEBAX 2533
	PLASTIC PEBAX 3533
	PLASTIC PEBAX 4011
	PLASTIC PEBAX 4033
	PLASTIC PEBAX 5512
	PLASTIC PEBAX 5533
	PLASTIC PEBAX 5562
	PLASTIC PEBAX 6312
	PLASTIC PEBAX 6333
	PLASTIC PEBAX SERIES 62
	PLASTIC RILSAN AECNO TL
	PLASTIC RILSAN AESNO P10 TL
	PLASTIC RILSAN AESNO P20 TL
	PLASTIC RILSAN AESNO P40 TL
	PLASTIC RILSAN AESNO TL
	PLASTIC RILSAN AMNO
	PLASTIC RILSAN AMNY
	PLASTIC RILSAN AUM 30
	PLASTIC RILSAN AZM 30
	PLASTIC RILSAN BECNO W3TL
	PLASTIC RILSAN BESNO
	PLASTIC RILSAN BESNO F15TL
	PLASTIC RILSAN BMN G8
	PLASTIC RILSAN BMNO
	PLASTIC RILSAN BMNY
ATOCHEM	PLASTIC RILSAN BZM23 BLK TL
	PLASTIC RILSAN BZM23G9
	PLASTIC RILSAN BZM43 BLK
	PLASTIC RILSAN BZM43G9
	PLASTIC RILSAN BZMO30
	PLASTIC RILSAN NYLON 12 MOLDING GRADE AZM23G9
	PLASTIC RILSAN NYLON 12 MOLDING GRADE AZN43G9
	PLASTIC RILSAN P40TL
	PLASTIC RILSAN SRL00
	PLASTIC VPC TYPE 2
AUBURN MFG	SPONGE RUBBER SILICONE
AUGAT INC	INSULATION MTA-1
	INSULATION MTA-2
	LAMIN EPOXY/GLASS AUGAT 8136URGI
	MOLD COMPOUND 514AG10D DAP
	MOLD COMPOUND DAP 514AGID YELLOW
	MOLD COMPOUND VALOX 420 SEO
AUSIMONT	PLASTIC ALGOFLON 27
	PLASTIC ALGOFLON D60V
	PLASTIC ALGOFLON DF1
	PLASTIC ALGOFLON E2
	PLASTIC ALGOFLON F2
	PLASTIC HALAR FEP
	PLASTIC HALAR PTFE
AUTOMATION IND	HOSE AIR DUCT FLEXFLYTE L1
	HOSE AIR DUCT FLEXFLYTE L9
AUTOMOTIVE FINISHES	COATING ZINC CHROMATE
AVCO SYSTEMS TEXTRON	COATING LATEX 1500 FLAMEREST
AVERY INTERNATIONAL	ADHESIVE CRACK 'N PEEL
	DESTRUX QC SEAL
	LABEL 8084-YG REMOVABLE
AVSCOA INC	RUBBER VITON FLUID RESISTANT
AVTEX FIBERS	FABRIC DURVIL/NOMEX
	FABRIC DURVIL/WOOL
	FABRIC RAYON/NOMEX
	FABRIC RAYON/WOOL
B C INSULATION	SLEEVING PVC POLYMER P/N 96M87264-1
B F GOODRICH	ADHESIVE A1216B
	ADHESIVE A1282B EPOXY
	ADHESIVE E1103
	ADHESIVE E2001 A/B
	ADHESIVE E2101 A/B
	ADHESIVE E2102 A/B
	ADHESIVE E2103 A/B
	ADHESIVE EE1102
	ADHESIVE EL2705
	ADHESIVE EPOXY WS1183 CB5
	ADHESIVE GOODRICH A1177 A/B EPOXY
	ADHESIVE PL410
	ADHESIVE PL420
	ADHESIVE PL425 EPOXY
	ADHESIVE PL430X EPOXY
	ADHESIVE PL601

MANUFACTURER	DESIGNATION
B F GOODRICH	ADHESIVE PL601 N/P FILM
	ADHESIVE PL603
	ADHESIVE PL604
	ADHESIVE PL605
	ADHESIVE PL606
	ADHESIVE PL618-1
	ADHESIVE PL618-2
	ADHESIVE PL639 N/P FILM
	ADHESIVE PL651
	ADHESIVE PL653EX
	ADHESIVE PL654GD
	ADHESIVE PL655
	ADHESIVE PL655 N/P FILM
	ADHESIVE PL659
	ADHESIVE PL717
	ADHESIVE PL741
	ADHESIVE PL750
	ADHESIVE PL751
	ADHESIVE PL760
	ADHESIVE PL770
	ADHESIVE PL776
	ADHESIVE PL777
	ADHESIVE PLASTILOCK 637
	ADHESIVE PLASTILOCK 729-3/728
	ADHESIVE PLASTILOCK 731 EPOXY
	ADHESIVE URETHANE 1246 A/B
	COATING A934BX AMINO SILANE
	COATING AEROCOAT AR7 SEE REPORT
	COATING AR7 ON CRES 304
	COATING AR7 ON KEL-F DISCS
	COATING AR7 ON STEEL DISCS
	COATING AR7 ON TEFLON TFE DISCS
	COATING AR7 WITH KRYTOX 240AC
	FILM TUFTANE 310 POLYURETHANE
	FILM TUFTANE 410 POLYURETHANE
	INSULATION WIRE ESTANE 58202
	MOLD COMPOUND GEON
	MULTI-LAYERED INSULATION AL/MYLAR/KEVLAR/ DACRON
	PLASTIC GEIB 8815
	PLASTIC GEON 2042
	PLASTIC GEON 82024
	PLASTIC GEON 82611
	PLASTIC GEON 83008
	PLASTIC GEON 83332
	PLASTIC GEON 83421
	PLASTIC GEON 83457
	PLASTIC GEON 83463
	PLASTIC GEON 83528
	PLASTIC GEON 83700
	PLASTIC GEON 83718
	PLASTIC GEON 83741
	PLASTIC GEON 83791
	PLASTIC GEON 83794
	PLASTIC GEON 86054
B F GOODRICH	PLASTIC GEON 86135
	PLASTIC GEON 86143
	PLASTIC GEON 86144
	PLASTIC GEON 86153
	PLASTIC GEON 86154
	PLASTIC GEON 86155
	PLASTIC GEON 86188
	PLASTIC GEON 8804FR
	PLASTIC GEON 8812
	PLASTIC GEON 8813
	PLASTIC GEON 8814
	PLASTIC GEON 8857
	PLASTIC GEON 8883
	PLASTIC GEON CIM 85856
	PLASTIC GEON CIM 87240
	PLASTIC GEON CIM 87241
	PLASTIC GEON CIM 87242
	PLASTIC GEON CIM 87300
	PLASTIC GEON CIM 87302
	PLASTIC GEON CIM 87317
	PLASTIC GEON CIM 87319
	PLASTIC GEON CIM 87322
	PLASTIC GEON CIM 87366
	PLASTIC GEON CIM 87371
	PLASTIC GEON CIM 87380
	RUBBER ESTANE 58013
	RUBBER ESTANE 58092
	RUBBER ESTANE 58110
	RUBBER ESTANE 58122
	RUBBER ESTANE 58130
	RUBBER ESTANE 58133
	RUBBER ESTANE 58134
	RUBBER ESTANE 58137
	RUBBER ESTANE 58206
	RUBBER ESTANE 58271
	RUBBER ESTANE 58277
	RUBBER ESTANE 58309
	RUBBER ESTANE 58311
	RUBBER ESTANE 58360
	RUBBER ESTANE 58370
	RUBBER ESTANE 58600
	RUBBER ESTANE 58610
	RUBBER ESTANE 58630
	RUBBER ESTANE 58810
	RUBBER ESTANE 58863
	RUBBER ESTANE 58881
	RUBBER ESTANE 58887
	WIRE ELEC ESTANE 58300
	WIRE ELEC ESTANE 58866 INSUL
B H HADLEY	RUBBER VITON A
BABCOCK & WILCOX	INSULATION KAOWOOL BULK A (INORG)
	INSULATION KAOWOOL CERAMIC/FOIL BACKING
	INSULATION KAOWOOL CERAMIC/SCRIM BK
	INSULATION KAOWOOL CONSORT ATF FOIL
	INSULATION KAOWOOL CONSORT ATF PLAIN

MSFC-HDBK-527 REV F 9999942 0006854 6

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
BACON	ADHESIVE ALLABOND 20/20
	ADHESIVE BACON FA8-BA5 COATED WITH SCOTCHCAST 280 B/A
	ADHESIVE BACON K31
	ADHESIVE BACON K50
	ADHESIVE BACON K5235
	ADHESIVE CONDUCTING 20/20
	ADHESIVE EPOXY FA8/BA5
	ADHESIVE EPOXY LCA9/BA5
	ADHESIVE FA1
	ADHESIVE FA13
	ADHESIVE FA14
	ADHESIVE FA21
	ADHESIVE FA8
	ADHESIVE FFA2
	ADHESIVE FFA5
	ADHESIVE FFA9
	ADHESIVE FLEXOBOND 329
	ADHESIVE FLEXOBOND 423
	ADHESIVE FLEXOBOND 425
	ADHESIVE JR228-1
	ADHESIVE JR228A
	ADHESIVE LCA127
	ADHESIVE LCA12XM
	ADHESIVE LCA14
	ADHESIVE LCA20
	ADHESIVE LCA21
	ADHESIVE LCA24
	ADHESIVE LCA4
	ADHESIVE LCA4/BA5 EPOXY
	ADHESIVE LCA4LV
	ADHESIVE LCA9
	ADHESIVE LGA1
	ADHESIVE P75 FOAM
	ADHESIVE P82 C
	ADHESIVE SC12
	ADHESIVE THERMAL CONDUCT SILICONE
BALL BROS RESEARCH	LUBE WET 37987
BALLY RIBBON MILLS	CABLE TIES NOMEX/POLYETHYLENE FC4101
	CORD NOMEX 150 LB
	CORD POLYESTER .0625 NATURAL
	FABRIC DACRON PACK CLOTH 6.3 OZ
	FABRIC GORTEX 1883C
	FABRIC GORTEX 2301
	FABRIC GORTEX TRICOT/PTFE
	FABRIC KELVAR 29
	FABRIC KEVLAR
	FABRIC KEVLAR 1813-2 WITH VITON
	FABRIC KEVLAR 9M03893/1813
	FABRIC KEVLAR U 2209
	FABRIC NOMEX 9476
	LACING TAPE BLACK
	LACING TAPE GORTEX
	LACING TAPE GORTEX .062 DIA
	LACING TAPE POLYESTER 2298

MANUFACTURER --	DESIGNATION
BALLY RIBBON MILLS	LACING TAPE POLYESTER RED
	NYLON 6/6
	TAPE LOOP-TAPE GORTEX
	TAPE LOOP-TAPE KEVLAR 1759
	TAPE LOOP-TAPE KEVLAR 2176
	TAPE LOOP-TAPE NOMEX
	TAPE LOOP-TAPE NYLON 1234
	TAPE NOMEX 1229
	TAPE NOMEX 9650
	TAPE NYLON 6707
	TAPE POLYESTER LOOP 2297
	TAPE TEFLON PATTERN 2338
	TAPE TFE
	THREAD DACRON "E"
	WEBBING DACRON
	WEBBING DACRON 1250LB
	WEBBING DACRON 1287
	WEBBING DACRON 1695
	WEBBING DACRON 2300 LB
	WEBBING DACRON 280
	WEBBING DACRON 300LB
	WEBBING DACRON 600 LB
	WEBBING DACRON 80 LB
	WEBBING DACRON 800 LB
	WEBBING DACRON 900 LB
	WEBBING KEVLAR 1000 LB
	WEBBING KEVLAR 10000 LB
	WEBBING KEVLAR 1758
	WEBBING KEVLAR 1813-2
	WEBBING KEVLAR 550 LB
	WEBBING KEVLAR 6000 LB
	WEBBING NOMEX
	WEBBING NOMEX 9476 FIREPROOFED
	WEBBING NOMEX 9960 FR
	WEBBING NOMEX 9981 FIREPROOFED
	WEBBING NOMEX TAPE
	WEBBING NOMEX/COATING FC4101-C-16
	WEBBING NYLON
	WEBBING NYLON 1000 LB
	WEBBING NYLON 2300 LB
	WEBBING NYLON 300 LB
	WEBBING NYLON 400 LB
	WEBBING NYLON 750 LB
	WEBBING NYLON 7774
	WEBBING NYLON 9000 LB
	WEBBING NYLON P8229
	WEBBING POLYESTER 1749
	WEBBING POLYESTER 1754
BARCEL WIRE AND CABLE	INSULATION BLACK FROM STRANDED ELECTRICAL WIRE
	WIRE ELEC FEP/POLYIMIDE TAPE
BARDEN CORP	BEARING BARDEN P/N 605172
BARRIER-WEAR	FABRIC NOMEX COVERALL (WASH/DRIED 25 TIMES)
BARRY CONTROLS	SHOCK ABSORBER N5205-TXE

MSFC-HDBK-527 REV F 9999942 0006855 8

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
BARRY WRIGHT CORP	COATING BARRY CONTROLS 103
	RUBBER SILICONE 6017 HI DAMP
	RUBBER SILICONE 77C 12640
	RUBBER SILICONE 92276
	RUBBER SILICONE CP6007
	RUBBER SILICONE E2022A HI-DAMP
	RUBBER SILICONE E2038 HI-DAMP
	RUBBER SILICONE E2041 HI-DAMP
BARWOOD MFG	SEALANT BARCO THERMOSET
BASD	FIBERGLASS/EPOXY EF2/59
	LAMIN EPOXY/GLASS S901
BASF STRUCTURAL MATERIALS	ADHESIVE 1117
	ADHESIVE 1137-1
	ADHESIVE 117
	ADHESIVE 1515-1
	ADHESIVE 306
	ADHESIVE 6603
	ADHESIVE 6607
	ADHESIVE 7820/20
	PLASTIC LUCOBIT 1210
	PLASTIC LURAN 358N
	PLASTIC LURAN 368R
	PLASTIC LURAN 378P
	PLASTIC LURAN 378P7
	PLASTIC LURAN 388S
	PLASTIC LURAN S728K
	PLASTIC LURAN S757R/RE
	PLASTIC LURAN S776S/SE
	PLASTIC LURAN SKR2843
	PLASTIC LURAN SKR2853/1
	PLASTIC LUVICAN
	PLASTIC NOVOLEN 1120HX
	PLASTIC NOVOLEN 1120LX
	PLASTIC NOVOLEN 1120NX
	PLASTIC NOVOLEN 1300E
	PLASTIC NOVOLEN 1300Z
	PLASTIC NOVOLEN 1320H
	PLASTIC NOVOLEN 1320L
	PLASTIC NOVOLEN 3300HX
	PLASTIC PALATAL P6 30/35% GLASS
	PLASTIC PALATAL P6 40/45% GLASS
	PLASTIC PALATAL P6 50/55% GLASS (IB)
	PLASTIC PALATAL P6 55/60% GLASS
	PLASTIC PALATAL P6 60/70% GLASS
	PLASTIC PALATAL P6 70/75% GLASS
	PLASTIC PALATAL P6 UNREINFORCED
	PLASTIC POLYSTYROL 143E
	PLASTIC POLYSTYROL 144C
	PLASTIC POLYSTYROL 158K
	PLASTIC POLYSTYROL 158KG6
	PLASTIC POLYSTYROL 165H
	PLASTIC POLYSTYROL 168N
	PLASTIC POLYSTYROL 427D
	PLASTIC POLYSTYROL 432B
	PLASTIC POLYSTYROL 454C
BASF STRUCTURAL MATERIALS	PLASTIC POLYSTYROL 454H
	PLASTIC POLYSTYROL 456M
	PLASTIC POLYSTYROL 466I
	PLASTIC POLYSTYROL 472C
	PLASTIC POLYSTYROL 473D
	PLASTIC POLYSTYROL 475K
	PLASTIC POLYSTYROL 476L
	PLASTIC POLYSTYROL KR2711
	PLASTIC POLYSTYROL KR2751
	PLASTIC POLYSTYROL KR2791
	PLASTIC POLYSTYROL SB2710
	PLASTIC STYRODUR 3000
	PLASTIC STYRODUR 4000
	PLASTIC STYRODUR 5000
	PLASTIC TERLURAN 828P
	PLASTIC TERLURAN 848S
	PLASTIC TERLURAN 857N
	PLASTIC TERLURAN 867M
	PLASTIC TERLURAN 877T/TE
	PLASTIC TERLURAN 886T
	PLASTIC TERLURAN 957SE
	PLASTIC TERLURAN 967K
	PLASTIC TERLURAN 978T
	PLASTIC TERLURAN 997VE
	PLASTIC TERLURAN KR2543
	PLASTIC TERLURAN KR2802/1
	PLASTIC TERLURAN KR2882
	PLASTIC ULTRADUR B4300G2
	PLASTIC ULTRADUR B4300G4
	PLASTIC ULTRADUR B4300G6
	PLASTIC ULTRADUR B4305G6
	PLASTIC ULTRADUR B4500
	PLASTIC ULTRADUR B4520
	PLASTIC ULTRADUR KR4015
	PLASTIC ULTRADUR KR4025
	PLASTIC ULTRADUR KR4035
	PLASTIC ULTRADUR KR4300K4
	PLASTIC ULTRAFORM H2200G5
	PLASTIC ULTRAFORM H2320
	PLASTIC ULTRAFORM N2320
	PLASTIC ULTRAFORM S2320
	PLASTIC ULTRAFORM W2320
	PLASTIC ULTRAMID A25
	PLASTIC ULTRAMID A3
	PLASTIC ULTRAMID A3 X 1G5
	PLASTIC ULTRAMID A3 X 1G7
	PLASTIC ULTRAMID A3 X G5
	PLASTIC ULTRAMID A3 X G7
	PLASTIC ULTRAMID A3EG10
	PLASTIC ULTRAMID A3EG5
	PLASTIC ULTRAMID A3EG6
	PLASTIC ULTRAMID A3EG7
	PLASTIC ULTRAMID A3G10
	PLASTIC ULTRAMID A3G6
	PLASTIC ULTRAMID A3G7

MSFC-HDBK-527 REV F 9999942 0006856 T

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
BASF STRUCTURAL MATERIALS	PLASTIC ULTRAMID A3GA
	PLASTIC ULTRAMID A3HG5
	PLASTIC ULTRAMID A3K
	PLASTIC ULTRAMID A3KN
	PLASTIC ULTRAMID A3R
	PLASTIC ULTRAMID A3SK
	PLASTIC ULTRAMID A3W
	PLASTIC ULTRAMID A3WG10
	PLASTIC ULTRAMID A3WG5
	PLASTIC ULTRAMID A3WG6
	PLASTIC ULTRAMID A3WG7
	PLASTIC ULTRAMID A4
	PLASTIC ULTRAMID A4H
	PLASTIC ULTRAMID A4K
	PLASTIC ULTRAMID A5
	PLASTIC ULTRAMID B3
	PLASTIC ULTRAMID B35
	PLASTIC ULTRAMID B35G3
	PLASTIC ULTRAMID B35SK
	PLASTIC ULTRAMID B35W
	PLASTIC ULTRAMID B3EG10
	PLASTIC ULTRAMID B3EG5
	PLASTIC ULTRAMID B3EG6
	PLASTIC ULTRAMID B3EG7
	PLASTIC ULTRAMID B3G10
	PLASTIC ULTRAMID B3G5
	PLASTIC ULTRAMID B3G5HS
	PLASTIC ULTRAMID B3G6
	PLASTIC ULTRAMID B3G6HS
	PLASTIC ULTRAMID B3G7
	PLASTIC ULTRAMID B3G7HS
	PLASTIC ULTRAMID B3K
	PLASTIC ULTRAMID B3L
	PLASTIC ULTRAMID B3S
	PLASTIC ULTRAMID B3WG10
	PLASTIC ULTRAMID B3WG5
	PLASTIC ULTRAMID B3WG6
	PLASTIC ULTRAMID B3WG7
	PLASTIC ULTRAMID B4
	PLASTIC ULTRAMID B4K
	PLASTIC ULTRAMID B5
	PLASTIC ULTRAMID B5W
	PLASTIC ULTRAMID KR1421
	PLASTIC ULTRAMID KR4442/300
	PLASTIC ULTRAMID KR4600
	PLASTIC ULTRAMID KR4601
	PLASTIC ULTRAMID S3
	PLASTIC ULTRAMID S3K
	PLASTIC ULTRAMID S4
	PLASTIC VINIDUR SZ6415
	PLASTIC VINIDUR SZ6415/VINOFLEX S6815
	PLASTIC VINOFLEX S6115
	PLASTIC VINOFLEX S6815
BAYSTAT	FILM ANTI-STATIC WITH GRIDS
BECKMAN INSTRUMENTS	COATING ENAMEL SEMIGLOSS GRAY
BEE CHEMICAL CO	INK BEE R222/T266 THINNER
BEECH AIRCRAFT	LAMIN EPOXY/GLASS E760A/7581/D6090
BEECHAM	ADHESIVE 999 CONSTRUCTION
	ADHESIVE CRAFTER'S EPOXY
	ADHESIVE CRAFTER'S FAST EPOXY
	ADHESIVE DAP 2000 CONSTRUCTION
	ADHESIVE DAP 4000 SUB FLOOR AND PLYWOOD
	ADHESIVE DAP FUNTAK
	ADHESIVE DAP GLUE STICK
	ADHESIVE DAP PERMABOND SUPER GLUE
	ADHESIVE DAP PERMABOND SUPER GLUE FOR WOOD AND LEATHER
	ADHESIVE DAPTAK REUSABLE
	ADHESIVE WELDWOOD ACRYLIC LATEX CONTACT CEMENT
	ADHESIVE WELDWOOD ALL WEATHER OUTDOOR CARPET
	ADHESIVE WELDWOOD CARPET CEMENT
	ADHESIVE WELDWOOD CONTACT CEMENT
	ADHESIVE WELDWOOD HEAVY DUTY WALLCOVERING
	ADHESIVE WELDWOOD MULTIPURPOSE FLOOR
	ADHESIVE WELDWOOD ORIGINAL CONTACT CEMENT
	ADHESIVE WELDWOOD RUBBER MENDER
	ADHESIVE WELDWOOD WALLCOVERING
BEEHIVE CLOTH MILLS	FABRIC COTTON/POLYESTER
BEI ELECTRONICS	ADHESIVE EPOXY R313
BEIERSDORF INC	BANDAGE ELASTIC ADHESIVE 1"WIDE
	CREME NIVEA SKIN CARE
BELDEN	CABLE COAX RG188
	FABRIC NOMEX HX-6157 SIZE F
	THREAD POLYESTER LOFTEX T16
	WIRE ELEC 2-WIRE CABLE
	WIRE ELEC POLYETHYLENE
	WIRE ELEC POLYURETHANE 8771
	WIRE ELEC PVC
	WIRE ELEC PVC INSULATED POLYAMIDE JACKET
	WIRE ELEC TEFLON TFE
BELL & HOWELL	RECORDER MARS 1400
BEMOL CORP	LUBE COMPOSITE ELEC CONDUCT
BEN HOGAN	FABRIC TEE SHIRT
BENDIX	ADHESIVE EPOXY 9-7844 B STAGE
	ADHESIVE SILICONE 9-5939-5
	CONNECTOR 40M RECEPTACLE/PLUG
	CONNECTOR ELEC 27473E8F35P
	CONNECTOR ELEC 27499E10F99P
	CONNECTOR ELEC 27508E12F35P
	CONNECTOR ELEC 3476L10-S5
	CONNECTOR ELEC JT06A-8-65(300)
	CONNECTOR ELEC PT06E-10-S5005
	CONNECTOR ELECTRICAL
	CONNECTOR ELECTRICAL 18-32 #4
	CONNECTOR ELECTRICAL 18-32P #1
	CONNECTOR ELECTRICAL 97E
	CONNECTOR MS3112E14-19P
	CONNECTOR PC BOARD 10-398050-1P

MSFC-HDBK-527 REV F 9999942 0006857 1

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
BENDIX	LACING TAPE NYLON BRAID
	MICROPHONE HANDHELD PLUG/CABLE
	MULTI-LAYERED TFE TAPE/CLAMP
	RECEPTACLE MS27503Y8E-35P
	RUBBER FLUOROSILICONE 9-6500
	SEALANT EPOXY HARD FILTER
	SINGLE LAYER TAPE/BENDIX CLAMP
	TAPE VITON-FLUOREL/CLAMP
BENTLEY HARRIS	CABLE COAXIAL THERMAX RGU142 OVERLAID WITH EXPANDO HR HALAR SLEEVING
	CABLE ELEC TFE/BEN-HAR GLUE
	COATING PYROLAC P123
	LACING CORD KEVLAR
	LACING TAPE F416 TEFLON COATED
	LACING TAPE GLASS/TFE
	LACING TAPE HT-15 LOC NOMEX
	LACING TAPE HT-20 LOC A NOMEX
	LACING TAPE HT-30 LOC A NOMEX
	LACING TAPE HT-30 LOC B GREEN
	LACING TAPE HT-30 LOC B NOMEX
	LACING TAPE HT-30 LOC B ORANGE
	LACING TAPE HT-30 NOMEX
	LACING TAPE HT-30 SPACE 1 INCH
	LACING TAPE HT-30 SPACE.5 INCH
	LACING TAPE HT-30-LOC A ORANGE
	LACING TAPE HT-30-TVS NOMEX
	LACING TAPE HT-30-VR
	LACING TAPE NOMEX
	LACING TAPE NOMEX ORANGE
	LACING TAPE NOMEX/VITON
	LACING TAPE PTFE ENAMELED
	LACING TAPE PYROLACE HT 30LOCC
	LACING TAPE PYROLACE STFE-40B
	LACING TAPE STFE-30B
	LACING TAPE STFE-80B
	LACING TAPE STUR-30
	LACING TAPE TG-30 20AWG
	RUBBER SILICONE 1258
	SLEEVING EXPANDO 686 TIGHTWEAVE
	POLYPHENYLENE SULFIDE
	TUBING ACRYL-A-FA1 FIBERGLASS
	TUBING BEN-HAR EXPANDO
	TUBING BEN-HAR ST
	TUBING BEN-HAR VITON 44
	TUBING FIBERGLASS
	TUBING PTFE NON-HEAT SHRINK
BERGQUIST	RUBBER SILICONE THERMAL CONDUCTIVE
	SEALANT SIL-PAD K10 INSULATOR KAPTON XT
	POLYIMIDE FILM WITH BORON NITRIDE FILLED
	SILICONE RUBBER
	SEALANT SIL-PAD K4 INSULATOR RUBBER WITH KAPTON XT FILM
BERMAN LEATHER CO	LEATHER COWHIDE BLACK 3 OZ
BEROL CORP	INK F30 BLACK
	PEN BEROL POROUS TIP/INK 7722
BEROL CORP	PEN FELT TIP F30J BLACK
BESTOBELL AVIATION	FABRIC SILICONE/GLASS GS200
BIC INC	INK BIC AF69
	INK BIC MARKING PM DELUX
	INK PM39 BLACK
	PEN BIC F39 BLACK
	PEN BIC FS11
	PEN PM BLACK/K-10 PAPER
BIDDLE CO	LUBE GREASE APIEZON H
	LUBE GREASE APIEZON L
	LUBE GREASE APIEZON T
	LUBE OIL APIEZON C
BIG 3	COATING PYROMARK 2500 HE BLACK
	COATING PYROMARK HE
	COATING TEMPILAQ GR800
	LABEL IDENTIFICATION TEMPILABEL BE2XXF
	TEMP SENSITIVE DOTS-PROPRIETAR
BIGGS CO	ADHESIVE EPOXY PUTTY A/B
BISCO PRODUCTS	SPONGE RUBBER SILICONE FOMEGA HT603
BISHOP GRAPHICS	TAPE ACETATE/LEXAN TP1-31
BLAISDELL MFG INC	LAMIN SHIM/POLYESTER ADHESIVE
BLH ELECTRONICS	ADHESIVE EPOXY 500
	ADHESIVE EPOXY EPY150
BLISTEX INC	LIPBALM BLISTIK
BLUE BELL PLASTICS	PLASTIC LEXAN ZELUX M GLASS FILLED
BMC INC	PLASTIC BMC100
	PLASTIC BMC1000
	PLASTIC BMC102
	PLASTIC BMC200
	PLASTIC BMC300
	PLASTIC BMC400
	PLASTIC BMC404
	PLASTIC BMC500
	PLASTIC BMC700
	PLASTIC BMC800
	PLASTIC BMC900
	PLASTIC BMC902
BOEING	RUBBER SILICONE BMS 1-70 GR 40
BONDED PRODUCTS	ADHESIVE EPISEAL 10-10
	ADHESIVE EPISEAL 20-20 EPOXY
	ADHESIVE EPISEAL 5 MINUTE EPOXY
	ADHESIVE EPISEAL IRON PUTTY
	ADHESIVE EPISEAL PLUS
	ADHESIVE MAINTZ N1000
	ADHESIVE WESTAC 718
BORDEN	ADHESIVE POLYCO 117-55
	ADHESIVE POLYCO 2113
	ADHESIVE POLYCO 2116
	ADHESIVE POLYCO 2123
	ADHESIVE POLYCO 2142
	ADHESIVE POLYCO 2149
	ADHESIVE POLYCO 2150
	ADHESIVE POLYCO 2186
	ADHESIVE POLYCO 571
	COATING KRYLON 1301 CLEAR

MSFC-HDBK-527 REV F 9999942 0006858 3

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
BORDEN	COATING KRYLON 150 CRYSTAL WHITE
	COATING KRYLON 1501 GLOSSY WHITE
	COATING KRYLON 1602
	COATING KRYLON LACQUER BLACK
	COATING KRYLON RED-ORANGE
	GLUE ELMERS
	LABEL KRYLON ACRYLIC SPRAY-ON
	PLASTIC BLENDING PVC RESINS VC260C
	PLASTIC BLENDING PVC RESINS VC260S
	PLASTIC BLENDING PVC RESINS VC260SS
	PLASTIC BLENDING PVC RESINS VC265
	PLASTIC COPOLYMER PVC RESIN VC113
	PLASTIC COPOLYMER PVC RESIN VC113K
	PLASTIC COPOLYMER PVC RESIN VC113R
	PLASTIC COPOLYMER PVC RESIN VC168
	PLASTIC COPOLYMER PVC RESIN VC171
	PLASTIC COPOLYMER PVC RESIN VC172
	PLASTIC HOMOPOLYMER PVC RESIN VC100PM
	PLASTIC HOMOPOLYMER PVC RESIN VC100RE
	PLASTIC HOMOPOLYMER PVC RESIN VC104PM
	PLASTIC HOMOPOLYMER PVC RESIN VC106PM
	PLASTIC HOMOPOLYMER PVC RESIN VC47B
	PLASTIC HOMOPOLYMER PVC RESIN VC54
	PLASTIC HOMOPOLYMER PVC RESIN VC58
	PLASTIC HOMOPOLYMER PVC RESIN VC95PM
	PLASTIC PASTE PVC RESINS 410M
	PLASTIC PASTE PVC RESINS VC-405
	PLASTIC PASTE PVC RESINS VC-411
	PLASTIC PASTE PVC RESINS VC-436/VC-437
	PLASTIC PASTE PVC RESINS VC-440
	PLASTIC PASTE PVC RESINS VC1069
	TAPE MYSTIK 6375 PAPER/PS GREEN
	TAPE MYSTIK 6402 PROPYLENE/ACRYLIC ADHESIVE
	TAPE MYSTIK 6466 DOUBLE COATED ADHESIVE
	TAPE MYSTIK 7000 GLASS/SILICONE ADHESIVE
	TAPE MYSTIK 7001 GLASS/SILICONE ADHESIVE
	TAPE MYSTIK 7100 GLASS/SILICONE ADHESIVE
	TAPE MYSTIK 7321 MYLAR/SILICONE
	TAPE MYSTIK 7341 POLYESTER/ACRYLIC ADHESIVE
	TAPE MYSTIK 7361 KAPTON/SILICONE ADHESIVE
	TAPE MYSTIK 7366 KAPTON/SILICONE ADHESIVE
	TAPE MYSTIK 7367 KAPTON/ACRYLIC ADHESIVE
	TAPE MYSTIK 7367/DC3140 COATING
	TAPE MYSTIK 7402 ALUMINUM SILICONE ADHESIVE
	TAPE MYSTIK 7452 ALUMINUM/ACRYLIC ADHESIVE
	TAPE MYSTIK 7453 AL ADHESIVE
	TAPE MYSTIK 7455 ADHESIVE
	TAPE MYSTIK 7503 TFE/SILICONE ADHESIVE
BORDEN DECAL CO	LABEL CAUTION FLEXCON MYLAR WITH ACRYLIC PS ADHESIVE V23 WITH NAZDAR MY111 BLACK AND PANTONE 803C FLUORESCENT YELLOW INK
BORDEN DECAL CO	LABEL IDENTIFICATION FLEXOFILM ACRYLIC PS ADHESIVE V23 WITH NAZDAR MY111 BLACK AND MY124 ORANGE INK
BORG WARNER	CYCOLOY KHS
	MOLD COMPOUND PROFAX 6527 POLYPROPYL
	PLASTIC CYCOLAC AR
	PLASTIC CYCOLAC DFA-R
	PLASTIC CYCOLAC DH
	PLASTIC CYCOLAC EP3510
	PLASTIC CYCOLAC EPB3570
	PLASTIC CYCOLAC ETS3540
	PLASTIC CYCOLAC GRT
	PLASTIC CYCOLAC GSM
	PLASTIC CYCOLAC HM
	PLASTIC CYCOLAC KJB
	PLASTIC CYCOLAC KJM
	PLASTIC CYCOLAC KJT
	PLASTIC CYCOLAC KJU
	PLASTIC CYCOLAC KJW
	PLASTIC CYCOLAC L
	PLASTIC CYCOLAC LXB
	PLASTIC CYCOLAC T
	PLASTIC CYCOLAC TA
	PLASTIC CYCOLAC X11
	PLASTIC CYCOLAC X15
	PLASTIC CYCOLAC X17
	PLASTIC CYCOLAC X37
	PLASTIC CYCOLAC Z48
	PLASTIC CYCOLAC Z86
	PLASTIC CYCOLAC ZA2
	PLASTIC CYCOLAC ZA4
	PLASTIC CYCOLAC ZA7
	PLASTIC CYCOLOY EHA
	PLASTIC CYCOVIN CTB
	PLASTIC CYCOVIN K20
	PLASTIC CYCOVIN K29
	PLASTIC PREVEX BIA
	PLASTIC PREVEX BJA
	PLASTIC PREVEX BJB
	PLASTIC PREVEX BJC
	PLASTIC PREVEX BJF
	PLASTIC PREVEX BJU
	PLASTIC PREVEX HC2
	PLASTIC PREVEX MPF
	PLASTIC PREVEX MPR
	PLASTIC PREVEX MVF
	PLASTIC PREVEX MVP
	PLASTIC PREVEX P2A
	PLASTIC PREVEX P3A
	PLASTIC PREVEX PMA
	PLASTIC PREVEX PQ1
	PLASTIC PREVEX PQA
	PLASTIC PREVEX V2A
	PLASTIC PREVEX V3A
	PLASTIC PREVEX VF1

MSFC-HDBK-527 REV F 9999942 0006859 5

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
BORG WARNER	PLASTIC PREVEX VFA
	PLASTIC PREVEX VGA
	PLASTIC PREVEX VJA
	PLASTIC PREVEX VJB
	PLASTIC PREVEX VK1
	PLASTIC PREVEX VKA
	PLASTIC PREVEX VM1
	PLASTIC PREVEX VMA
	PLASTIC PREVEX VQ1
	PLASTIC PREVEX VQA
	PLASTIC PREVEX W20
	PLASTIC PREVEX W30
	PLASTIC PREVEX W40
	PLASTIC PREVEX W50
	PLASTIC PREVEX W70
	PLASTIC PROLOY HC3
BOSTIK FINCH	ADHESIVE BOSTIK 1007
	ADHESIVE BOSTIK 1008
	ADHESIVE BOSTIK 1009A/1008B
	ADHESIVE BOSTIK 1015
	ADHESIVE BOSTIK 1076
	ADHESIVE BOSTIK 1096
	ADHESIVE BOSTIK 1101
	ADHESIVE BOSTIK 1142
	ADHESIVE BOSTIK 1205
	ADHESIVE BOSTIK 1205/B9072
	ADHESIVE BOSTIK 1252
	ADHESIVE BOSTIK 1315
	ADHESIVE BOSTIK 1372
	ADHESIVE BOSTIK 1376
	ADHESIVE BOSTIK 1398
	ADHESIVE BOSTIK 1515
	ADHESIVE BOSTIK 1530
	ADHESIVE BOSTIK 1600
	ADHESIVE BOSTIK 2000
	ADHESIVE BOSTIK 2009
	ADHESIVE BOSTIK 2315
	ADHESIVE BOSTIK 2363
	ADHESIVE BOSTIK 2378
	ADHESIVE BOSTIK 2425
	ADHESIVE BOSTIK 3000
	ADHESIVE BOSTIK 320
	ADHESIVE BOSTIK 4000
	ADHESIVE BOSTIK 4025
	ADHESIVE BOSTIK 4101
	ADHESIVE BOSTIK 4165
	ADHESIVE BOSTIK 4252
	ADHESIVE BOSTIK 4342
	ADHESIVE BOSTIK 620
	ADHESIVE BOSTIK 6323
	ADHESIVE BOSTIK 6330
	ADHESIVE BOSTIK 6368
	ADHESIVE BOSTIK 7008
	ADHESIVE BOSTIK 7376
	ADHESIVE BOSTIK 7431

MANUFACTURER	DESIGNATION
BOSTIK FINCH	ADHESIVE BOSTIK 7432
	ADHESIVE BOSTIK 7433
	ADHESIVE BOSTIK 7434
	ADHESIVE BOSTIK 7435
	ADHESIVE BOSTIK 8230
	ADHESIVE BOSTIK 8323
	ADHESIVE BOSTIK 8330
	ADHESIVE BOSTIK 8363
	ADHESIVE BOSTIK 8375
	ADHESIVE BOSTIK 8376
	ADHESIVE BOSTIK 8377
	ADHESIVE BOSTIK 8378
	ADHESIVE BOSTIK 8379
	ADHESIVE BOSTIK 920
	ADHESIVE BOSTIK 9732
	ADHESIVE THERMOGRIP 6363
	ADHESIVE THERMOGRIP 6363-15
	ADHESIVE THERMOGRIP 6368-15
	COATING 443-3-1 WHITE EPOXY
	COATING 443-3-17 BLACK EPOXY
	COATING 453-4-5/C212 POLYIMIDE EPOXY
	COATING 453-4-BLUE POLYAMIDE SEMI-GLOSS EPOXY 212
	COATING 463-12-19 EPOXY PRIMER
	COATING 463-12-19 PRIMER
	COATING 463-12-8/643-1-1 EPOXY
	COATING 463-12-8/643-2-20 EPOXY
	COATING 463-12-8/C-116 EPOXY
	COATING 463-12-8/PRIMER
	COATING 463-3-100/C-118 PRIMER WHITE
	COATING 463-3-209 EPOXY
	COATING 463-3-33 TC/515-700 PRIMER
	COATING 463-4-4 PRIMER EPOXY
	COATING 463-6-3 GREEN EPOXY
	COATING 463-6-5 PRIMER/463-3-8 EPOXY
	COATING 463-7-26/A276/X-369
	COATING 643-1-1 POLYURETHANE
	COATING 683-3-3Y POLYURETHANE
	COATING CAT-A-LAC 463-3-8/C118
	COATING CONDUCTIVE 463-6-14
	COATING EPOXY 463-12-8/4593-30
	COATING EPOXY 463-12-8/A276
	COATING EPOXY AMINE
	COATING EPOXY/POLYAMIDE CONVERT
BOURNS INC	ADHESIVE EPOXY DGBA
BOYD INDUS RUBBER	FABRIC FIBERGLASS/VITON 5707
	HOSE SILICONE PUROSIL 70-087
	HOSE SILICONE PUROSIL 80-100
	RUBBER BUNA S
	RUBBER COHRLASTIC R10460 SILICONE
	RUBBER SILICONE HARDNESS SHORE "A" 55-65
	RUBBER SILICONE NOC ZZ-R-765
	SPONGE RUBBER SILICONE
BOYD INDUSTRY RUBBER	RUBBER BOYD NR35
	RUBBER BOYD OR50

MSFC-HDBK-527 REV F 9999942 0006860 1

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
BOYD INDUSTRY RUBBER	RUBBER BOYD OR60
	RUBBER BOYD OR70
	RUBBER BUNA N NBR50
	RUBBER BUNA N NBR60
	RUBBER BUNA N NBR70
	RUBBER BUNA S SBR75
	RUBBER BUTYL IIR55
	RUBBER EPT60
	RUBBER NEOPRENE CR MC
	RUBBER NEOPRENE CR45
	RUBBER NEOPRENE CR50
	RUBBER NEOPRENE CR60
	RUBBER NEOPRENE CR70
	RUBBER SILICONE SI400
	RUBBER SILICONE SI500
	RUBBER SILICONE SI600
	RUBBER SILICONE SI700
BP PERFORMANCE POLYMERS, INC	PLASTIC BLANE 2150
	PLASTIC BLANE 2153
	PLASTIC BLANE 2202
	PLASTIC BLANE 2234
	PLASTIC BLANE 2249
	PLASTIC BLANE 309
	PLASTIC BLANE 375
	PLASTIC BLANE 7191
	PLASTIC BLANE 8100
	PLASTIC BLANE 8105
	PLASTIC BLANE 830
	PLASTIC BLANE 851
	PLASTIC BLANE 9148
	PLASTIC BLANE 9202-1
	PLASTIC TPR1720D
	PLASTIC TPR1900D
	PLASTIC TPR5190
	PLASTIC TPR5260
	PLASTIC TPR5280
	PLASTIC TPR5290
	PLASTIC TPP5470
	PLASTIC TPR5490
	PLASTIC TPR5591
	PLASTIC TPR5595
	PLASTIC TPR5680
BRADEN STUPHIN	INK A-M CS174C/JCP K10 BLACK
BRADY MFG	TUBING POLYOLEFIN B322 HST
BRAILSFORD & CO	BLOWER BRAILSFORD MODEL TB1-1
BRAND REX CORP	CABLE FIBER OPTIC OC-1050
BRAY OIL CO	CLEANER BRAYCOTE 137
	LUBE CPD GRAPHITE/PETROLATUM
	LUBE GREASE BRAYCO 640AC
	LUBE GREASE BRAYCO 800 SERIES
	LUBE GREASE BRAYCO 814Z
	LUBE GREASE BRAYCO 815Z FLUORINATED
	LUBE GREASE BRAYCO 885B
	LUBE GREASE BRAYCO NPT4
	LUBE GREASE BRAYCOTE 236
BRAY OIL CO	LUBE GREASE BRAYCOTE 3L-38RP
	LUBE GREASE BRAYCOTE 3L-38ZN
	LUBE GREASE BRAYCOTE 600
	LUBE GREASE BRAYCOTE 601
	LUBE GREASE BRAYCOTE 601 B/L
	LUBE GREASE BRAYCOTE 6275
	LUBE GREASE BRAYCOTE 804
	LUBE GREASE BRAYCOTE 804A
	LUBE GREASE BRAYCOTE 805
	LUBE GREASE BRAYCOTE 805A
	LUBE GREASE BRAYCOTE 805B2
	LUBE GREASE BRAYCOTE 806
	LUBE GREASE BRAYCOTE 806A
BRENTWOOD PLASTICS	FILM POLYETHYLENE FR
BRIGGS RUBBER PROD	RUBBER VITON 1097
	RUBBER VITON SHORE A
BRISTOL MYERS CO	DEODORANT SOLID ANTI-PERSPIRNT
BROOKSTONE	POTTING COMPOUND EPOXY PUTTY 3249 A/B
BRUEL & KJAER	METER SOUND LEVEL 2215
BRUNSON INSTRUMENT	LABEL 721 POLYESTER FILM WITH B196 PS ADHES
BRUNSWICK	COATING FILAMENT WOUND KELVAR
	COATING POLANE TOPCOAT/KEVLAR
	COMPOSITE KEVLAR/EPOXY WRAP
	COMPOSITE REINFORCEMENT
	FILTER NOMEX MEMBRANE
	THREAD CRES 300 SERIES
	THREAD CRES 304 MF-A1 28/61/5Z
BUCHANAN	TERMINAL STRIP 221 PHENOLIC
BUCKEYE RUBBER	RUBBER SILICONE GR 2
BUEHLER LTD	COATING SILCARB/POLYETHYLENE
BURCOTT MILLS	FABRIC NOMEX 90043/46
BURLINGTON	FABRIC FIBERGLASS/SILANE I399
	FABRIC KEVLAR 49
	FABRIC KEVLAR 49 STYLE 26435
	FABRIC POLYESTER STYLE67004/08
	FABRIC POPLIN COTTON AND DACRON
	FABRIC UTOPIA STYLE #540982
BURNDY	CONNECTOR ELECTRICAL
BURRON MEDICAL	SYRINGE 60 CC POLYPROPYLENE/SILICONE
BUSSMAN	MOLD COMPOUND POLYESTER/GLASS MAI-60
C & C PACKINGS	RUBBER VITON A 017-ESQ
	RUBBER VITON FLUID RESISTANT
	RUBBER VITON V14
C & R SILK SCREEN	LABEL IDENTIFICATION 126 FABRIC
	LABEL IDENTIFICATION ILC UNSPRAYED NOT TYPED
	LABEL KRYLON ACRYLIC SPRAY-ON
C D LA MOREE CO	INSULATION ELECTRICAL RAG PAPER
C E CONOVER	RUBBER VITON A V709-90
	RUBBER VITON O-RING
	SEALANT RUBBER 27980
C H BEXTER & SONS CO	TISSUE DRY AND POLISHING
C-LINE PRODUCTS INC	LAMIN CLEER-ADHERE 65001
CABOT CORP	POWDER CAB-O-SIL M5

MSFC-HDBK-527 REV F 9999942 0006861 3

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
CABOT CORP	SILICA CAB-O-SIL M-5
CADILLAC PLASTICS	ADHESIVE CADCO BA400
	ADHESIVE CADCO BA500
	ADHESIVE CADCO PS18
	ADHESIVE CADCO PS30
	FILM TEFLON TFE
	KEL-F 81
	KEL-F CTFE UNPLASTICIZED
	KYNAR PLASTIC FLUORIDE
	NYLON 6/6
	PLASTIC CADCO ABS NATURAL
	PLASTIC CADCO ACRYLIC PMM CAST
	PLASTIC CADCO CAST ACRYLIC
	PLASTIC CADCO LEXAN POLYCARBONATE EXTRUDED
	PLASTIC CADCO MD POLYAMIDE MDS2 FILL
	PLASTIC CADCO NSM POLYAMIDE FILLED 6
	PLASTIC CADCO NYLON CBL
	PLASTIC CADCO NYLON CMD
	PLASTIC CADCO NYLON CNT
	PLASTIC CADCO POLYPROPYLENE NATURAL
	PLASTIC CADCO POLYSTYRENE HI-IMPACT
	PLASTIC CADCO PVC RIGID
	PLASTIC CADCO TEFLON PTFE VIRGIN
	PLASTIC CADCO TYPE 6
	PLASTIC CADCO TYPE 6/6
	PLASTIC CADCO UHMW
	PLASTIC CAST NYLON POLYAMIDE TYPE 6
	PLASTIC DELRIN
	PLASTIC DELRIN 150
	PLASTIC DELRIN 550
	PLASTIC DELRIN AF POLYACETAL FILLED HOMO
	PLASTIC OILON PV80 POLYACETAL FILLED HOMO
	PLASTIC POLYACETAL HOMOPOLYMER
	TEFLON TFE VIRGIN
CAL POLYMERS INC	RUBBER CALTHANE 1400
	RUBBER CALTHANE 1700
	RUBBER CALTHANE 1900
	RUBBER CALTHANE ND1100
	RUBBER CALTHANE ND2300
	RUBBER CALTHANE ND3200
	RUBBER CALTHANE NF1200
	RUBBER CALTHANE NF1300
	RUBBER CALTHANE NF1300-60A
	RUBBER CALTHANE NF1500
	RUBBER CALTHANE NF310W
CALIFORNIA PLASTECK	COATING CPA5197 GREY EPOXY
	COATING CPC3864 WHITE EPOXY
	COATING EPOXY GRAY 36118
	COATING EPOXY WHITE 37875
	CORD NYLON
	TEFLON TFE VIRGIN
CALLAHAN MINING	DUCT NEOPRENE IMPREG CTN FAB
CALLERY CHEMICAL	ADHESIVE FOAM POLYURETHANE
CALMONT	WIRE ELEC PVC
	WIRE ELEC URETHANE 29 AWG

MANUFACTURER	DESIGNATION
CALSPAN	CALSPAN SEAL SETS 67/151007
CALVARY CHEMICAL	INSULATION FOAM POLYURETHANE SFP-237
CAMBION	INSULATION TERMINAL 570-1994-XX0100
CAMIE CO	INSULATION FOAM URETHANE/PS ADHES
CANNON	INK CANON NP270F/JCP E20PAPER
	TOWELS 78% COTTON/22% POLYESTER
CARBOLINE	COATING CARBOLINE NO 10 SEE RPT
	COATING CARBOLINE NO 11 SEE RPT
	COATING CARBOLINE NO 12 SEE RPT
	COATING CARBOLINE NO 13 SEE RPT
	COATING CARBOLINE NO 14 SEE RPT
	COATING CARBOLINE NO 15 SEE RPT
	COATING CARBOLINE NO 16 SEE RPT
	COATING CARBOLINE NO 17 SEE RPT
	COATING CARBOLINE NO 18 SEE RPT
	COATING CARBOLINE NO 30 SEE RPT
	COATING CARBOLINE NO 31 SEE RPT
	COATING CARBOLINE NO 32 SEE RPT
	COATING CARBOLINE NO 33 SEE RPT
CARBORUNDUM	BARRIER FIBERTRAX HOTBOARD
	FABRIC KYNOL
	INSULATION FIBERFRAX 970A CERAMIC
CARDINAL PAINT CO	COATING 5078-5 CLEAR ENAMEL
	COATING ENAMEL 5002 FED 595027038
	COATING POLYURETHANE BLACK
	INK BLADDER MARKING URETHANE
CARDIO PULMONARY INSTRUMENTS	NOSECLIP P/N 85103531
CARLETON CONTROLS	KEL-F 81
	PNEUMATIC SURGE TEST FIXTURE
	RUBBER SILICONE S614-80
	TEFLON TFE VIRGIN
	VALVE OXYGEN CHECK
CARLISLE CORP	CABLE ELEC TFE/VARGLAS SLEEVE
	WIRE ELEC E7371001
	WIRE ELEC TEFLON TFE
CARNEGIE TEXTILE	FABRIC FLANNEL 545 COTTON WHITE
CAROLINA FABRIC	FABRIC 520/S920 SILANE FINISH
CASTALL INC	ADHESIVE CASTALL 110 A/B
	ADHESIVE CASTALL 1520/E34 EPOXY
	ADHESIVE CASTALL 1520/HT70
	ADHESIVE CASTALL 1520/RT 1
	ADHESIVE CASTALL 1520/RT 7
	ADHESIVE CASTALL 2009
	ADHESIVE CASTALL 310 A/B
	ADHESIVE CASTALL 341
	ADHESIVE CASTALL 343 EPOXY
	ADHESIVE CASTALL 4874
	ADHESIVE CASTALL 4875
	ADHESIVE CASTALL 6612
	ADHESIVE CASTALL A
	ADHESIVE CASTALL A343
	ADHESIVE CASTALL D
	ADHESIVE CASTALL E
	ADHESIVE CASTALL E100

MSFC-HDBK-527 REV F 9999942 0006862 5

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
CASTALL INC	ADHESIVE CASTALL E105
	ADHESIVE CASTALL E106
	ADHESIVE CASTALL E1530/E34
	ADHESIVE CASTALL E300
	ADHESIVE CASTALL E301
	ADHESIVE CASTALL E301AD
	ADHESIVE CASTALL E301KT
	ADHESIVE CASTALL E341
	ADHESIVE CASTALL E341FR
	ADHESIVE CASTALL E401
	ADHESIVE CASTALL E403
	ADHESIVE CASTALL E409
	ADHESIVE CASTALL E435/E34
	ADHESIVE CASTALL E463/E34
	ADHESIVE CASTALL E464/E34
	ADHESIVE CASTALL E466/E34
	ADHESIVE CASTALL E480 A
	ADHESIVE CASTALL E482 A
	ADHESIVE CASTALL E483 A
	ADHESIVE CASTALL E492/E34 FR
	ADHESIVE CASTALL F
	ADHESIVE CASTALL G
	ADHESIVE CASTALL H
	ADHESIVE CASTALL J/E34
	ADHESIVE CASTALL J/RT 1
	ADHESIVE CASTALL J/RT 7A
	ADHESIVE CASTALL K/E34
	ADHESIVE CASTALL K/RT 7A HI-IMPACT EPOXY
	ADHESIVE CASTALL QUICK CURE
	ADHESIVE CASTALL S1277
	ADHESIVE CASTALL U2001
	ADHESIVE CASTALL U2002
	ADHESIVE CASTALL U2003
	ADHESIVE CASTALL U2004
	ADHESIVE CASTALL U2006
	ADHESIVE CASTALL U2007
	ADHESIVE CASTALL U2008
	ADHESIVE CASTALL U2009
	ADHESIVE CASTALL U2010
	ADHESIVE CASTALL U2012
	ADHESIVE CASTALL U2015
	ADHESIVE CASTALL U2017
	ADHESIVE CASTALL U2018
	ADHESIVE CASTALL U2019
	ADHESIVE CASTALL U2020
	ADHESIVE CASTALL U2020FR
	ADHESIVE CASTALL U2024
	ADHESIVE CASTALL U2028
	ADHESIVE CASTALL U2032
	ADHESIVE CASTALL U2036
	ADHESIVE CASTALL U2040
	ADHESIVE CASTALL U2044
	ADHESIVE CASTALL U2048
	ADHESIVE CASTALL U2052
	COATING 1295 EPOXY

MANUFACTURER	DESIGNATION
CASTALL INC	LUBE GREASE CASTALL 800 SILICONE
	POTTING COMPOUND CASTALL 301/RT1
	POTTING COMPOUND CASTALL A301/E34
CATALINA PACIFIC TEX	FABRIC NOMEX K-GUARD CLR#21302
CELANESE	ADHESIVE EPIREZ 510
	ADHESIVE EPON 826/BDE/T6040
	ADHESIVE METLBOND 1113
	ADHESIVE METLBOND 329-7
	CELCON G-C25 ACETAL/25% GLASS
	CELCON M-90-24 ACETAL POLYMER
	CELCON WHITE
	COATING EPICEL 3 EPOXY/CURE AGENT U
	FABRIC AIRC73300-233
	FABRIC POLYBENZIMIDAZOLE (PBI)
	HOSE SILICONE/PBI POS BREATHER
	PASTIC CELCON MC90
	PLASTIC CELANEX 2000
	PLASTIC CELANEX 2000K
	PLASTIC CELANEX 2002
	PLASTIC CELANEX 2002K
	PLASTIC CELANEX 2003K
	PLASTIC CELANEX 2012
	PLASTIC CELANEX 3112
	PLASTIC CELANEX 3200
	PLASTIC CELANEX 3210
	PLASTIC CELANEX 3211
	PLASTIC CELANEX 3300
	PLASTIC CELANEX 3310
	PLASTIC CELANEX 3310/GL/POLYE
	PLASTIC CELANEX 3311
	PLASTIC CELANEX 3400
	PLASTIC CELANEX 4300
	PLASTIC CELANEX 4330
	PLASTIC CELANEX 5300
	PLASTIC CELANEX 6400
	PLASTIC CELANEX 7700
	PLASTIC CELCON AS270
	PLASTIC CELCON AS450
	PLASTIC CELCON GB25
	PLASTIC CELCON GC25A GLASS COUPLED
	PLASTIC CELCON M25
	PLASTIC CELCON M270
	PLASTIC CELCON M90
	PLASTIC CELCON MC270HM
	PLASTIC CELCON MC90HM
	PLASTIC CELCON WR25
	PLASTIC CELCON WR90
	PLASTIC DURALOY 2000
	PLASTIC DURALOY 2100
	PLASTIC DUREL 400
	PLASTIC DUREL 410
	PLASTIC DUREL 420
	PLASTIC DUREL 430
	PLASTIC DUREL 440
	PLASTIC NYLON 1000

MSFC-HDBK-527 REV F 9999942 0006863 7

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
CELANESE	PLASTIC NYLON 1000-1
	PLASTIC NYLON 1000-2
	PLASTIC NYLON 1000-4
	PLASTIC NYLON 1000-6
	PLASTIC NYLON 1003
	PLASTIC NYLON 1003-1
	PLASTIC NYLON 1003-2
	PLASTIC NYLON 1003-4
	PLASTIC NYLON 1003-6
	PLASTIC NYLON 1100
	PLASTIC NYLON 1200
	PLASTIC NYLON 1300
	PLASTIC NYLON 1310
	PLASTIC NYLON 1310-1
	PLASTIC NYLON 1310-2
	PLASTIC NYLON 1310-4
	PLASTIC NYLON 1310-6
	PLASTIC NYLON 1400
	PLASTIC NYLON 1400-1
	PLASTIC NYLON 1400-2
	PLASTIC NYLON 1403-1
	PLASTIC NYLON 1403-2
	PLASTIC NYLON 1500
	PLASTIC NYLON 1500-1
	PLASTIC NYLON 1500-2
	PLASTIC NYLON 1503-1
	PLASTIC NYLON 1503-2
	PLASTIC NYLON 1600
	PLASTIC NYLON 1600-1
	PLASTIC NYLON 1600-2
	PLASTIC NYLON 7010
	PLASTIC NYLON 7013
	PLASTIC NYLON 7020
	PLASTIC NYLON 7023
	PLASTIC NYLON 7030
	PLASTIC NYLON 7033
	PLASTIC NYLON 7420
	PLASTIC NYLON 7423
	PLASTIC NYLON N186
	PLASTIC NYLON N224
CELESCO	IGNTN GRANULES-BORON PTSM NITR
CELLPACK	TUBING CEVOLITE X651
CELLU-PAK CONVERTERS	PAPER TELETYPEWRITER CARBON
CENTRAL LAB INC	COATING MEPCO FLEX
	COATING MEPCO FR14 CONFORMAL
CERMALLOY	ADHESIVE CERMALLOY 5100
	ADHESIVE CERMALLOY 5200
	ADHESIVE CERMALLOY 5200F
	ADHESIVE CERMALLOY 5300
	ADHESIVE CERMALLOY 5500
	ADHESIVE CERMALLOY PC200S
	ADHESIVE CERMALLOY PC300S
	ADHESIVE CERMALLOY T2000 EPOXY
	ADHESIVE CERMALLOY T2100 EPOXY
	ADHESIVE CERMALLOY T2100T

MANUFACTURER	DESIGNATION
CERMALLOY	ADHESIVE CERMALLOY T2110
	ADHESIVE CERMALLOY T2110T
	ADHESIVE CERMALLOY T2200
	ADHESIVE CERMALLOY T2210
	ADHESIVE CERMALLOY T2300
	ADHESIVE CERMALLOY T2310
	ADHESIVE CERMALLOY T2800
	ADHESIVE CERMALLOY T2810
	ADHESIVE CERMALLOY T2811
	ADHESIVE CERMALLOY T2900
	ADHESIVE CERMALLOY UVC500
	ADHESIVE CERMALLOY UVI100
CERRO WIRE & CABLE	WIRE ELEC TEFLON TFE
CHAMPLAIN CABLE CORP	WIRE ELEC ETFE TEFZEL
	WIRE ELEC FEP/POLYIMIDE TAPE
CHARLES BRIGHT	RUBBER NEOPRENE BC CWB10
CHASE TECHNOLOGY	RUBBER SILICONE NOC ZZ-R-765
	SPONGE RUBBER SILICONE PR855 FR
	SPONGE RUBBER SILICONE PR855-2 FR
CHEMELEX	HEATER AUTOTRACE 10PTV1 18 AWG
CHEMICAL CORPORATION OF AMERICA	PLASTIC CHEMCOR EMULSION 2-67A
	PLASTIC CHEMCOR PARAFFIN EMULSION 135-50
	PLASTIC CHEMCOR POLY EMULSION 286
	PLASTIC CHEMCOR ZAC
	PLASTIC DISPERSION 8-31B
	PLASTIC EMULSION XL20
	PLASTIC OPACIFIER 341
	PLASTIC PARIFIN EMULSION 135-40
	PLASTIC PEN CLEAR
	PLASTIC PEN-1031
	PLASTIC POLY EMULSION 10 N30
	PLASTIC POLY EMULSION 121 N30
	PLASTIC POLY EMULSION 153 N35
	PLASTIC POLY EMULSION 261 A35
	PLASTIC POLY EMULSION 316 N30
	PLASTIC POLY EMULSION 325 N35
	PLASTIC POLY EMULSION 330 N35
	PLASTIC POLY EMULSION 371 N30
	PLASTIC POLY EMULSION 392 A25
	PLASTIC POLY EMULSION 392 C30
	PLASTIC POLY EMULSION 392 LE30
	PLASTIC POLY EMULSION 392 N25
	PLASTIC POLY EMULSION 392 N35
	PLASTIC POLY EMULSION 43 N40
	PLASTIC POLY EMULSION 540 A25
	PLASTIC POLY EMULSION 540 N30
	PLASTIC POLY EMULSION 540 N40
	PLASTIC POLY EMULSION 629 A30
	PLASTIC POLY EMULSION 629 N04
	PLASTIC POLY EMULSION 656 A25
CHEMICAL DEVELOPMENT CO	ADHESIVE CEMENT PS18 ACRYLIC
CHEMICAL FABRICS	CHEMFABRICS 1
	CHEMFABRICS 2
	CHEMFABRICS 3

MSFC-HDBK-527 REV F 9999942 0006864 9

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
CHEMICAL FABRICS	FABRIC TFE GLASS TG 4060
CHEMICAL TECHNOLOGY	COATING CTL/C15 EPOXY WHITE 27875
	COATING CTL15/C15 CAT EPOXY BLACK
CHEMLINE INDUSTRIES	MASK SOLDER PC401 CLEAR
	MASK SOLDER PC401 GREEN
	MASK SOLDER PC501 CLEAR
	MASK SOLDER PC501-GREEN
CHEMPLAST	ADHESIVE CHEMGRIP
	FILM KEMIT 5518 POLYIMIDE/TFE/LUBRICANT
	KEL-F 81
	KEL-F 81 EXPANDED/BLUE BEADING
	LUBE FLUOROGLIDE GRADE FB
	NYLON 6/6
	PLASTIC CTFE
	PLASTIC ECTFE
	PLASTIC ETFE
	PLASTIC PFA
	ROD CHEMFLUOR TFE VIRGIN EXT
	TAPE TEFLON TY10 SILICONE
	TEFLON TFE VIRGIN
	TUBING FEP TEFLON
	TUBING KORVEX FEP HS
	TUBING KORVEX TFE HS
	TUBING PTFE HST
	TUBING TEFLON TFE HST
CHEMPRENE	FABRIC NEOPRENE RIPSTOP COATED
	FABRIC NEOPRENE/NYLON CRP21757
	FABRIC NYLON RIPSTOP UNCOATED
	FABRIC NYLON/NEOPRENE COATED
CHEMRAY COATINGS	COATING ALKYD GLOSS ENAMEL 12246
CHEMSECO	ADHESIVE SEALUM FM100
	ADHESIVE SEALUM SM501
	ADHESIVE SEALUM SM506
	ADHESIVE SEALUM SM507
	ADHESIVE SEALUM SM508
	ADHESIVE SEALUM SM509
	ADHESIVE SEALUM SM532
CHEMTEK INC	FABRIC 1213 TY1 CL1 NEOPRENE-COATED NYLON
CHEMTRONICS	COATING KONFORM SILICONE
	INSULATION FOAM CHEMLON 100TA NRL2-2
	INSULATION FOAM CHEMLON 100TA PC
	INSULATION FOAM CHEMLON 103
	INSULATION FOAM CHEMLON 200 FF NRL25
	INSULATION FOAM CHEMLON 203
	INSULATION FOAM CHEMLON 403
	INSULATION FOAM CHEMLON 500FC POLYIMIDE
	INSULATION FOAM CHEMLON 503
	INSULATION FOAM CHEMLON 504 POLYIMIDE
	INSULATION FOAM CHEMLON POLYIMIDE
	INSULATION FOAM POLYIMIDE CHEMLON 701
CHESEBROUGH-PONDS	LIPBALM CONSTANT CARE
CHEVRON CHEMICAL	PLASTIC EA3000
	PLASTIC EA3100
	PLASTIC EA3200
	PLASTIC EA6740
CHEVRON CHEMICAL	PLASTIC EA6750
	PLASTIC EA6765
	PLASTIC EA9400
	PLASTIC EB6780
	PLASTIC EC2100
	PLASTIC EC6600
	PLASTIC EC6760
	PLASTIC EC6770
	PLASTIC EH6600
	PLASTIC GEON 87237
	PLASTIC GEON 87239
	PLASTIC GEON 87321
	PLASTIC GEON 87341
	PLASTIC GEON 87342
	PLASTIC HID9112
	PLASTIC HID9114
	PLASTIC HID9116
	PLASTIC HID9122
	PLASTIC HID9402
	PLASTIC HID9406
	PLASTIC HID9410
	PLASTIC HID9412/9413
	PLASTIC HID9416
	PLASTIC HID9450
	PLASTIC HID9512/9513
	PLASTIC KN220
	PLASTIC KN226
	PLASTIC KN230
	PLASTIC MA3200
	PLASTIC MA5000
	PLASTIC MA6800
	PLASTIC MA9000
	PLASTIC MC2100
	PLASTIC MC3100
	PLASTIC MC3500
	PLASTIC MC3600
	PLASTIC MC3700
	PLASTIC MC5161
	PLASTIC MC6561
	PLASTIC MC6800
	PLASTIC MC9540
	PLASTIC MD9520
	PLASTIC PE 1007
	PLASTIC PE 1008.5
	PLASTIC PE 117A
	PLASTIC PE 1205
	PLASTIC PE 1207
	PLASTIC PE 1220
	PLASTIC PE 1260
	PLASTIC PE 1400
	PLASTIC PE 1408.5
	PLASTIC PE 1409
	PLASTIC PE 1412
	PLASTIC PE 4538A
	PLASTIC PE 4538B

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
CHEVRON CHEMICAL	PLASTIC PE 5104
	PLASTIC PE1117A
CHOMERICS	ADHESIVE CHOBOND 1029
	ADHESIVE CHOBOND 1030
	ADHESIVE CHOBOND 1030/1086 SILICONE
	ADHESIVE CHOBOND 1035
	ADHESIVE CHOBOND 1038
	ADHESIVE CHOBOND 320
	ADHESIVE CHOBOND 350A/B WITH 1086PRI
	ADHESIVE CHOBOND 360-18
	ADHESIVE CHOBOND 360-20
	ADHESIVE CHOBOND 360-208
	ADHESIVE CHOBOND 4660
	ADHESIVE CHOBOND 4669
	ADHESIVE CHOBOND 584 CONDUCTIVE EPOXY
	ADHESIVE CHOBOND 584-208
	ADHESIVE CHOBOND 584-29 CON/EPOXY
	ADHESIVE CHOBOND 592
	ADHESIVE CHOMERICS 360 EPOXY
	COATING CHOSHIELD 596 A/B EPOXY
	COATING CHOSHIELD EPOXY/AG FILLD
	INSULATION CHOTRAP CM26-3
	LAMIN EPOXY CL522
	RUBBER CHOFOAM 1501
	RUBBER CHOSEAL 1214 WITH AG/SILICONE
	RUBBER CHOSEAL 1217 FLUORO SILICONE/AG FILLED
	RUBBER CHOSEAL 1221 AG/FLUOROSILICONE
	RUBBER CHOSEAL 1250REI/SIL/AG
	RUBBER SILICONE CHOSEAL 1212
	RUBBER SILICONE CHOSEAL 1215
	RUBBER SILICONE CHOSEAL 1220
	RUBBER SILICONE CHOSEAL 1224
	RUBBER SILICONE CHOSEAL 1285
	RUBBER SILICONE CHOSEAL 1287
	RUBBER SILICONE CHOSEAL 1350
	RUBBER SILICONE CHOSEAL 1401
	RUBBER SILICONE CHOSEAL 1485
	RUBBER SILICONE CHOTHERM 1641
	RUBBER SILICONE CHOTHERM 1642
	RUBBER SILICONE CHOTHERM 1661
	RUBBER SILICONE CHOTHERM 1661 WITH CHOBOND 320
	RUBBER SILICONE CHOTHERM 1663
	RUBBER SILICONE CHOTHERM 1664
	RUBBER SILICONE CHOTHERM 1665
	RUBBER SILICONE CHOTHERM 1666
	RUBBER SILICONE CHOTHERM 1667
	RUBBER SILICONE CHOTHERM 1671
	RUBBER SILICONE CHOTHERM 1673R
	TAPE CHOFOIL 101 COPPER FOIL
CHROMALLOY AMERICAN	BATTERY DRY K308A P4-01-0008
CHROMAX CORP	FOAM INTERFLO HIGH MOLECULAR WEIGHT POLYETHYLENE HYDROPHOBIC FLAME RETARDANT
CHROMAX CORP	INSULATION FOAM INTERFLO HIGH MOLECULAR WEIGHT POLYETHYLENE
CIBA-GEIGY	ADHESIVE ARALDITE 101
	ADHESIVE ARALDITE 1138/HY906/DY062
	ADHESIVE ARALDITE 138/HV998
	ADHESIVE ARALDITE 465 A80
	ADHESIVE ARALDITE 465A-80-1
	ADHESIVE ARALDITE 465A-80-2
	ADHESIVE ARALDITE 502
	ADHESIVE ARALDITE 506
	ADHESIVE ARALDITE 507-1
	ADHESIVE ARALDITE 507-2
	ADHESIVE ARALDITE 507-3
	ADHESIVE ARALDITE 507-4
	ADHESIVE ARALDITE 509
	ADHESIVE ARALDITE 6004-1
	ADHESIVE ARALDITE 6004-2
	ADHESIVE ARALDITE 6005/906
	ADHESIVE ARALDITE 6010/AROMATIC DIAMINE
	ADHESIVE ARALDITE 6010/DICY
	ADHESIVE ARALDITE 6010/HY940/EHT939
	ADHESIVE ARALDITE 6010/POLYAMIDE
	ADHESIVE ARALDITE 6010/TETA
	ADHESIVE ARALDITE 6020-1
	ADHESIVE ARALDITE 6020-2
	ADHESIVE ARALDITE 6020-3
	ADHESIVE ARALDITE 6060-1
	ADHESIVE ARALDITE 6060-2
	ADHESIVE ARALDITE 6060-3
	ADHESIVE ARALDITE 7071/DICY
	ADHESIVE ARALDITE 7071/POLYAMIDE
	ADHESIVE ARALDITE AV100
	ADHESIVE ARALDITE CY8043-2
	ADHESIVE ARALDITE DY027-3
	ADHESIVE ARALDITE EPN1138/BR3MEA
	ADHESIVE ARALDITE EPN1138/HT972
	ADHESIVE ARALDITE EPN1138/HY907/DY062
	ADHESIVE ARALDITE EPN1138/NADIC METHYL ANHYDRIDE N/N-DIMETHYL BENAYLAMIN
	ADHESIVE ARALDITE GY005-3
	ADHESIVE ARALDITE GY6005-1
	ADHESIVE ARALDITE GY6005-2
	ADHESIVE ARALDITE GY6005-3
	ADHESIVE ARALDITE GY6005-4
	ADHESIVE ARALDITE MY720/HY906/FORM VAR 7/70
	ADHESIVE ARALDITE MY720/HY972/FORM VAR 7/70
	ADHESIVE ARALDITE RP138
	ADHESIVE BSL 119 PRIMER
	ADHESIVE BSL 208/5 FOAM
	ADHESIVE BSL 312
	ADHESIVE BSL 319
	ADHESIVE CY8043-1
	ADHESIVE ECN1235/906/MBDMA

MSFC-HDBK-527 REV F 9999942 0006866 2

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
CIBA-GEIGY	ADHESIVE ECN1235/907/066
	ADHESIVE ECN1235/BF3MEA
	ADHESIVE ECN1273/906/MBDMA
	ADHESIVE ECN1299/906
	ADHESIVE ECN1299/906/MNDMA
	ADHESIVE EPN1139/HT907/DY062
	ADHESIVE REDUX 410NA EPOXY
	ANTENNA MATL KEV/KAP/EPOXY
	COATING BSL 112 PRIMER
	LAMIN EPOXY/GLASS XYLOK 210
	PAPER PHOTO CIBACROME
	PLASTIC CG1310R/RP1520H
	PLASTIC CGL1310R/RP1520H
	PLASTIC CGL1320R/RP1500H
	PLASTIC CGL1320R/RP1520H
	PLASTIC FASTOOL RP3265
	PLASTIC RP-1220
	PLASTIC RP-1225
	PLASTIC RP-1710
	PLASTIC RP-1720
	PLASTIC RP-1774
	PLASTIC RP-3209-1
	PLASTIC RP-3209-2
	PLASTIC RP-3215-1
	PLASTIC RP-3215-2
	PLASTIC RP-3215-3
	PLASTIC RP-3253
	PLASTIC RP-3261
	PLASTIC RP-3262
	PLASTIC RP-3266 45/55
	PLASTIC RP-3266 5-/45
	PLASTIC RP-3266 50/50
	PLASTIC RP-3269
	PLASTIC RP-3269-1
	PLASTIC RP-3270 CASTING
	PLASTIC RP-3270 LAMINATING
	PLASTIC RP-4003
	PLASTIC RP-4005/1500H
	PLASTIC RP-4036/RP-1500H
	PLASTIC RP-4104R/1500H
	PLASTIC RP1118
	PLASTIC RP1125
	PLASTIC RP1126
	PLASTIC RP1129
	PLASTIC RP1700
	PLASTIC RP306
	PLASTIC RP3260
	PLASTIC RP4018R/RP1520H
	PLASTIC RP4026/RP1501
	PLASTIC TDT-177-15
	PLASTIC TDT-177-62
	POTTING COMPOUND REN RP6401A POLYURETHANE BLUE
	POTTING COMPOUND REN RP6402A POLYURETHANE RED
CIBA-GEIGY	TUBING 4100 EPOXY POLYAMINE
CIRCLE SEAL	RUBBER VITON FLUID RESISTANT
	SEALANT CIRCLE P/N 32834
	TEFLON TFE VIRGIN
	TEFLON TFE/25% GLASS
CIRCUIT INDUSTRIES	LAMIN EPOXY/GLASS
CIRCUIT MATERIALS	FILM CMC122 KAPTON ADHESIVE COATED
CLAREMONT FLOCK CORP	FABRIC COTTON 591 FLOCK
CLARK INC	SEALANT METASEAL 19V5M POLYESTER
CLARK SCHWEBEL CORP	FABRIC KEVLAR 343
CLAUD S GORDON CO	TUBING GLASS/SILICONE K26-2-305
CLEAN ROOM PRODUCTS	FILM CRP POLYETHYLENE ANTISTATIC P/N B0214
	SPONGE ESTER POLYURETHANE
COAST MFG & SUPPLY	LAMIN F131-21 GLASS/SILICONE
COAST PROSEAL	ADHESIVE EPON 828/VERSAMID 125
	ADHESIVE EPON 828/VERSAMID 140
	ADHESIVE EPON 828/VERSAMID 828/VERSAMID 125
	ADHESIVE PROSEAL 828 EPOXY
	ADHESIVE PROSEAL 829 EPOXY
	ADHESIVE PROSEAL 840 EPOXY
	SEALANT POLYSULFIDE PROSEAL 890
	SEALANT PROSEAL 247A/B URETH
COASTCRAFT RUBBER CO	RUBBER CNR RESISTAZINE 88
COATS & CLARK	THREAD COTTON 2 CORE
COILHOSE PNEUMATICS	HOSE NYLON COIL N344
COLE PARMER	ADHESIVE EPOXY EXTRA FAST SETTING
COLGATE-PALMOLIVE	CREAM SHAVE BRUSHLESS
	SEALANT COLAD 984 A/B
	TOWELETTES WASH 'N DRI
COLLINS & AIKMAN	FABRIC ANCHORAGE 2
	FABRIC ANCHORAGE 2 BLUE 69/1211
COLONIAL PRINTING	COATING INK/ADHESIVE ON LEXAN
	INK POLY PRINT 45NL75/45NL99
	INK SERIES 3900 HT9040
	INK SERIES 4500 45NL75/82853
COLONIAL PRINTING/ GENERAL ELECTRIC	INK 9900 ON LEXAN
COLORITE PLASTICS CO	ADHESIVE QUICKBOND 513
	PLASTIC 5311-19
	PLASTIC TENITE PROPIONATE FORMULA 311 H5
	PLASTIC UNICHEM 10015-XRAY
	PLASTIC UNICHEM 1010G015
	PLASTIC UNICHEM 1011G-015
	PLASTIC UNICHEM 1011G05
	PLASTIC UNICHEM 1015G-05
	PLASTIC UNICHEM 1015G015
	PLASTIC UNICHEM 105
	PLASTIC UNICHEM 1080G
	PLASTIC UNICHEM 1104
	PLASTIC UNICHEM 1104-05
	PLASTIC UNICHEM 1114
	PLASTIC UNICHEM 1114G-05
	PLASTIC UNICHEM 1115G-05
	PLASTIC UNICHEM 1116

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
COLORITE PLASTICS CO	PLASTIC UNICHEM 1116G-015
	PLASTIC UNICHEM 1280A-02
	PLASTIC UNICHEM 1280G-015
	PLASTIC UNICHEM 1304-02
	PLASTIC UNICHEM 1304G
	PLASTIC UNICHEM 1314 NATURAL
	PLASTIC UNICHEM 1316-05
	PLASTIC UNICHEM 1317
	PLASTIC UNICHEM 1416-05
	PLASTIC UNICHEM 3876
	PLASTIC UNICHEM 3879
	PLASTIC UNICHEM 40-105
	PLASTIC UNICHEM 4011
	PLASTIC UNICHEM 4012G-015
	PLASTIC UNICHEM 4060
	PLASTIC UNICHEM 4060A
	PLASTIC UNICHEM 4075
	PLASTIC UNICHEM 4075H
	PLASTIC UNICHEM 4075H FR
	PLASTIC UNICHEM 4114
	PLASTIC UNICHEM 4160
	PLASTIC UNICHEM 4160 LT/FR-1
	PLASTIC UNICHEM 4160C
	PLASTIC UNICHEM 4160LT
	PLASTIC UNICHEM 4170
	PLASTIC UNICHEM 4195
	PLASTIC UNICHEM 4196
	PLASTIC UNICHEM 4260-75
	PLASTIC UNICHEM 4260-80
	PLASTIC UNICHEM 4260-85
	PLASTIC UNICHEM 4260-90
	PLASTIC UNICHEM 4260-95
	PLASTIC UNICHEM 4260A-66
	PLASTIC UNICHEM 4261-40
	PLASTIC UNICHEM 4261-80
	PLASTIC UNICHEM 4511
	PLASTIC UNICHEM 4543
	PLASTIC UNICHEM 4875
	PLASTIC UNICHEM 5011
	PLASTIC UNICHEM 5012G-015
	PLASTIC UNICHEM 5012G-05
	PLASTIC UNICHEM 5160-40
	PLASTIC UNICHEM 5211
	PLASTIC UNICHEM 5311-38
	PLASTIC UNICHEM 5376
	PLASTIC UNICHEM 5376FFR
	PLASTIC UNICHEM 5433
	PLASTIC UNICHEM 5500
	PLASTIC UNICHEM 5511
	PLASTIC UNICHEM 5511-02
	PLASTIC UNICHEM 5543
	PLASTIC UNICHEM 5545
	PLASTIC UNICHEM 5611
	PLASTIC UNICHEM 5612
	PLASTIC UNICHEM 5790

MANUFACTURER	DESIGNATION
COLORITE PLASTICS CO	PLASTIC UNICHEM 5790A
	PLASTIC UNICHEM 5811
	PLASTIC UNICHEM 5812
	PLASTIC UNICHEM 6011
	PLASTIC UNICHEM 6011A-02
	PLASTIC UNICHEM 6011G-015
	PLASTIC UNICHEM 6012G-015
	PLASTIC UNICHEM 6014 D FOAM
	PLASTIC UNICHEM 6022 NATURAL
	PLASTIC UNICHEM 6033
	PLASTIC UNICHEM 6091
	PLASTIC UNICHEM 6093
	PLASTIC UNICHEM 6111A
	PLASTIC UNICHEM 6111B
	PLASTIC UNICHEM 6193F
	PLASTIC UNICHEM 6283
	PLASTIC UNICHEM 6476
	PLASTIC UNICHEM 6500
	PLASTIC UNICHEM 6507
	PLASTIC UNICHEM 6511
	PLASTIC UNICHEM 6511-02
	PLASTIC UNICHEM 6511A-02
	PLASTIC UNICHEM 6512
	PLASTIC UNICHEM 6512G-015
	PLASTIC UNICHEM 6574
	PLASTIC UNICHEM 6575
	PLASTIC UNICHEM 6576
	PLASTIC UNICHEM 6742
	PLASTIC UNICHEM 6743
	PLASTIC UNICHEM 6743 CLEAR
	PLASTIC UNICHEM 6811
	PLASTIC UNICHEM 6811-02 BUSCH
	PLASTIC UNICHEM 6812-02
	PLASTIC UNICHEM 6812A-02
	PLASTIC UNICHEM 6812G-015
	PLASTIC UNICHEM 7000
	PLASTIC UNICHEM 7003
	PLASTIC UNICHEM 7003 WHITE
	PLASTIC UNICHEM 7011
	PLASTIC UNICHEM 7011CZ-02
	PLASTIC UNICHEM 7011G-015
	PLASTIC UNICHEM 7012
	PLASTIC UNICHEM 7012C-02
	PLASTIC UNICHEM 7012G-015
	PLASTIC UNICHEM 7033
	PLASTIC UNICHEM 7074
	PLASTIC UNICHEM 7075
	PLASTIC UNICHEM 7090B
	PLASTIC UNICHEM 7099
	PLASTIC UNICHEM 7224B
	PLASTIC UNICHEM 7233
	PLASTIC UNICHEM 7233H
	PLASTIC UNICHEM 7305
	PLASTIC UNICHEM 7342
	PLASTIC UNICHEM 7342 CLEAR

MSFC-HDBK-527 REV F 9999942 0006868 6

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
COLORITE PLASTICS CO	PLASTIC UNICHEM 7380 CLEAR
	PLASTIC UNICHEM 7411-0
	PLASTIC UNICHEM 7444
	PLASTIC UNICHEM 7444D
	PLASTIC UNICHEM 75-103B
	PLASTIC UNICHEM 7500
	PLASTIC UNICHEM 7503
	PLASTIC UNICHEM 7511
	PLASTIC UNICHEM 7511B-02
	PLASTIC UNICHEM 7512G-015
	PLASTIC UNICHEM 7533
	PLASTIC UNICHEM 7533A FR
	PLASTIC UNICHEM 7575
	PLASTIC UNICHEM 7580
	PLASTIC UNICHEM 7588 CLEAR BLUE
	PLASTIC UNICHEM 7712-G-015
	PLASTIC UNICHEM 7712F-NBBM
	PLASTIC UNICHEM 7805
	PLASTIC UNICHEM 7805 (CLEAR)
	PLASTIC UNICHEM 7810
	PLASTIC UNICHEM 7811
	PLASTIC UNICHEM 7811-30
	PLASTIC UNICHEM 7812G-015
	PLASTIC UNICHEM 7813
	PLASTIC UNICHEM 7815
	PLASTIC UNICHEM 7815G-015
	PLASTIC UNICHEM 7834
	PLASTIC UNICHEM 7849
	PLASTIC UNICHEM 7933H
	PLASTIC UNICHEM 80-111K
	PLASTIC UNICHEM 8000
	PLASTIC UNICHEM 8000 FR-UV
	PLASTIC UNICHEM 8000-02
	PLASTIC UNICHEM 8005
	PLASTIC UNICHEM 8005-90
	PLASTIC UNICHEM 8005C
	PLASTIC UNICHEM 8006 MG
	PLASTIC UNICHEM 8011
	PLASTIC UNICHEM 8011 RADIO-OPAQUE
	PLASTIC UNICHEM 8011-02
	PLASTIC UNICHEM 8011A-02
	PLASTIC UNICHEM 8011AG-015
	PLASTIC UNICHEM 8011G-015
	PLASTIC UNICHEM 8011K-02
	PLASTIC UNICHEM 8012
	PLASTIC UNICHEM 8012G-015
	PLASTIC UNICHEM 8012N-02
	PLASTIC UNICHEM 8033
	PLASTIC UNICHEM 8034
	PLASTIC UNICHEM 8060
	PLASTIC UNICHEM 8080
	PLASTIC UNICHEM 8083
	PLASTIC UNICHEM 8085
	PLASTIC UNICHEM 8090
	PLASTIC UNICHEM 8090C

MANUFACTURER	DESIGNATION
COLORITE PLASTICS CO	PLASTIC UNICHEM 8091
	PLASTIC UNICHEM 8092
	PLASTIC UNICHEM 8093 NATURAL
	PLASTIC UNICHEM 8099
	PLASTIC UNICHEM 8180FR-1
	PLASTIC UNICHEM 8190
	PLASTIC UNICHEM 8190FR-1
	PLASTIC UNICHEM 82-378D
	PLASTIC UNICHEM 8200 FR WHITE
	PLASTIC UNICHEM 8200FR
	PLASTIC UNICHEM 8205
	PLASTIC UNICHEM 8299
	PLASTIC UNICHEM 8311
	PLASTIC UNICHEM 8311A
	PLASTIC UNICHEM 8311A-02
	PLASTIC UNICHEM 8312B-02
	PLASTIC UNICHEM 8312G-015
	PLASTIC UNICHEM 84-209C
	PLASTIC UNICHEM 84-369
	PLASTIC UNICHEM 84-421D
	PLASTIC UNICHEM 85-268F
	PLASTIC UNICHEM 8500
	PLASTIC UNICHEM 8511
	PLASTIC UNICHEM 8511-02
	PLASTIC UNICHEM 8511A-02
	PLASTIC UNICHEM 8512G-015
	PLASTIC UNICHEM 8512N-02
	PLASTIC UNICHEM 8533
	PLASTIC UNICHEM 8560
	PLASTIC UNICHEM 8562
	PLASTIC UNICHEM 8580
	PLASTIC UNICHEM 8588
	PLASTIC UNICHEM 8614
	PLASTIC UNICHEM 8634
	PLASTIC UNICHEM 8681
	PLASTIC UNICHEM 8703
	PLASTIC UNICHEM 8705
	PLASTIC UNICHEM 8705-FR
	PLASTIC UNICHEM 8711A-02
	PLASTIC UNICHEM 8715
	PLASTIC UNICHEM 8733
	PLASTIC UNICHEM 8804
	PLASTIC UNICHEM 8901
	PLASTIC UNICHEM 8990
	PLASTIC UNICHEM 9000
	PLASTIC UNICHEM 9001C-015
	PLASTIC UNICHEM 9003
	PLASTIC UNICHEM 9005
	PLASTIC UNICHEM 9011
	PLASTIC UNICHEM 9012G-015
	PLASTIC UNICHEM 9012N-02
	PLASTIC UNICHEM 9033
	PLASTIC UNICHEM 9034A-FRLS
	PLASTIC UNICHEM 9090B
	PLASTIC UNICHEM 9172C

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
COLORITE PLASTICS CO	PLASTIC UNICHEM 9314A
	PLASTIC UNICHEM 9500
	PLASTIC UNICHEM 9511
	PLASTIC UNICHEM 9511A-02
	PLASTIC UNICHEM 9512G-015
	PLASTIC UNICHEM 9554-F4
	PLASTIC UNICHEM 9611
	PLASTIC UNICHEM 9612G-015
	PLASTIC UNICHEM 9614
	PLASTIC UNICHEM 9712A-02-HS
	PLASTIC UNICHEM 9805
	PLASTIC UNICHEM 9811
	PLASTIC UNICHEM 9811-015
	PLASTIC UNICHEM 9811-15
	PLASTIC UNICHEM 9812G-015
	PLASTIC UNICHEM 9813
	PLASTIC UNICHEM 9813 (BLACK,WHITE,BROWN)
	PLASTIC UNICHEM 9813 (GREENS)
	PLASTIC UNICHEM 9814
	PLASTIC UNICHEM 9833
	PLASTIC UNICHEM 9904
	PLASTIC UNICHEM 9904-03
	PLASTIC UNICHEM AA7093
	PLASTIC UNICHEM AG8757E
	PLASTIC UNICHEM CUM8882
COLORTONE	INK CERAMIC WITH IRON OXIDE INORGANIC
COLUMBIA CEMENT	ADHESIVE CONBOND
	ADHESIVE CONBOND 1560 N/F
	ADHESIVE CONBOND 1736 N/F SPRAY
	ADHESIVE CONBOND 2103 N/F
	ADHESIVE CONBOND 2153
	ADHESIVE CONBOND 2214 N/F SUPER SPRAY
	ADHESIVE CONBOND 2448
	ADHESIVE CONBOND 2466
	ADHESIVE CONBOND 2620
	ADHESIVE CONBOND 272SP
	ADHESIVE CONBOND 2849 N/F SPRAY
	ADHESIVE CONBOND 2960
	ADHESIVE CONBOND 2979
	ADHESIVE CONBOND 3004
	ADHESIVE CONBOND 310 WATER BASED CONTACT
	ADHESIVE CONBOND 330
	ADHESIVE CONBOND 360
	ADHESIVE CONBOND 773
	ADHESIVE CONBOND 773-40
	ADHESIVE CONBOND 985
	ADHESIVE CONBOND CONTACT CEMENT
	ADHESIVE KWIKSTIK 1676 N/F
	ADHESIVE KWIKSTIK 516
	ADHESIVE KWIKSTIK 747
	ADHESIVE PANELGRIP 1229
COLUMBIA TECH CORP	COATING HUMISEAL 1A20 POLYURETHANE
	COATING HUMISEAL 1A33 POLYURETHANE
	COATING HUMISEAL 1B12 ACRYLIC
	COATING HUMISEAL 1B31 ACRYLIC
COLUMBIA TECH CORP	COATING HUMISEAL 1B73
	COATING HUMISEAL 2A64A/B POLYURETHANE
	COATING HUMISEAL 2A72 POLYURETHANE
COLYER	WIRE ELEC PEEK (POLYETHER-ETHERKETONE)
	WIRE ELEC TEFLON PFA
COMALLOY INTERNATIONAL CORP	COMALLOY 110-1520
	PLASTIC COMALLOY 110-1120
	PLASTIC COMALLOY 110-1140
	PLASTIC COMALLOY 110-1220
	PLASTIC COMALLOY 110-1240
	PLASTIC COMALLOY 110-1540
	PLASTIC COMALLOY 110-3010
	PLASTIC COMALLOY 110-3020
	PLASTIC COMALLOY 110-3030
	PLASTIC COMALLOY 110-3040
	PLASTIC COMALLOY 120-2430
	PLASTIC COMALLOY 130-3020
	PLASTIC COMALLOY 130-3040
	PLASTIC COMALLOY 140-2140
	PLASTIC COMALLOY 140-2250
	PLASTIC COMALLOY 140-2355
	PLASTIC COMALLOY 140-3010
	PLASTIC COMALLOY 140-3020
	PLASTIC COMALLOY 140-3030
	PLASTIC COMALLOY 140-3040
	PLASTIC COMALLOY 170-3020
	PLASTIC COMALLOY 170-3030
	PLASTIC COMALLOY 170-3040
	PLASTIC COMALLOY 210-3020
	PLASTIC COMALLOY 210-3030
	PLASTIC COMALLOY 220-3010
	PLASTIC COMALLOY 220-3020
	PLASTIC COMALLOY 220-3030
	PLASTIC COMALLOY 220-3040
	PLASTIC COMALLOY 240-3020
	PLASTIC COMALLOY 240-3030
	PLASTIC COMALLOY 240-3040
	PLASTIC COMALLOY 260-3020
	PLASTIC COMALLOY 260-3030
	PLASTIC COMALLOY 310-3010
	PLASTIC COMALLOY 310-3015
	PLASTIC COMALLOY 310-3020
	PLASTIC COMALLOY 410-2140
	PLASTIC COMALLOY 410-2140-100
	PLASTIC COMALLOY 410-2250
	PLASTIC COMALLOY 410-2250-100
	PLASTIC COMALLOY 410-2355
	PLASTIC COMALLOY 410-3015
	PLASTIC COMALLOY 410-3015-100
	PLASTIC COMALLOY 410-3030
	PLASTIC COMALLOY 410-3030-100
	PLASTIC COMALLOY 410-3045
	PLASTIC COMALLOY 410-3045-100
	PLASTIC COMALLOY 410-3055
	PLASTIC COMALLOY 510-1515

MSFC-HDBK-527 REV F 9999942 0006870 4

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
COMALLOY INTERNATIONAL CORP	PLASTIC COMALLOY 510-2615
	PLASTIC COMALLOY 510-3010
	PLASTIC COMALLOY 510-3024
	PLASTIC COMALLOY 510-3030
	PLASTIC COMALLOY 510-3040
	PLASTIC COMALLOY 515-1000
	PLASTIC COMALLOY 610-2140
	PLASTIC COMALLOY 610-2250
	PLASTIC COMALLOY 610-2355
	PLASTIC COMALLOY 610-3013
	PLASTIC COMALLOY 610-3020
	PLASTIC COMALLOY 610-3033
	PLASTIC COMALLOY 610-3043
	PLASTIC COMALLOY 610-3050
	PLASTIC COMALLOY 620-1540
	PLASTIC COMALLOY 620-2140
	PLASTIC COMALLOY 620-2140-100
	PLASTIC COMALLOY 620-2250
	PLASTIC COMALLOY 620-2355
	PLASTIC COMALLOY 620-3013
	PLASTIC COMALLOY 620-3013-100
	PLASTIC COMALLOY 620-3020
	PLASTIC COMALLOY 620-3020-100
	PLASTIC COMALLOY 620-3033-100
	PLASTIC COMALLOY 620-3043
	PLASTIC COMALLOY 620-3043-100
	PLASTIC COMALLOY 620-3050
	PLASTIC COMALLOY 640-2140
	PLASTIC COMALLOY 640-2250
	PLASTIC COMALLOY 640-2355
	PLASTIC COMALLOY 640-3020
	PLASTIC COMALLOY 640-3033
	PLASTIC COMALLOY 640-3043
	PLASTIC COMALLOY 640-3050
	PLASTIC COMALLOY 660-3013
	PLASTIC COMALLOY 660-3020
	PLASTIC COMALLOY 660-3033
	PLASTIC COMALLOY 660-3043
	PLASTIC COMALLOY 660-3050
	PLASTIC COMALLOY 710-2140
	PLASTIC COMALLOY 710-2250
	PLASTIC COMALLOY 710-2355
	PLASTIC COMALLOY 710-3030
	PLASTIC COMALLOY 710-3040
	PLASTIC COMALLOY 710-3050
	PLASTIC COMALLOY 740-3020
	PLASTIC COMALLOY 740-3030
	PLASTIC COMALLOY 740-3040
	PLASTIC COMALLOY HILOY 610
COMMERCIAL CHEMICAL	ADHESIVE EPO 114 GEL
	ADHESIVE EPO 114 T2 LIQUID
	ADHESIVE EPO 114 TI LIQUID
	ADHESIVE EPO 116 LOW MODULUS
	ADHESIVE EPO ALL-PURPOSE
	ADHESIVE MASTIC EPOXY

MANUFACTURER	DESIGNATION
COMMERCIAL KANES	SCREEN TEFLON FEP/FIBERGLASS
COMMERCIAL PLASTICS	WARMER FOOD NEMA G-11 EPOXY/GL
COMPOSITE OPTICS	LAMIN EPOXY/GRAPHITE FIBERITE HY-E2030D
COMPOUNDING TECHNOLOGY (CTI)	PLASTIC AN20GF
	PLASTIC AN30GF
	PLASTIC AN40GF
	PLASTIC AS15CF1000
	PLASTIC AT20GF
	PLASTIC AT30GF
	PLASTIC AT40GF
	PLASTIC CTI ABS AS10GF
	PLASTIC CTI ABS AS20GF
	PLASTIC CTI ABS AS30GF
	PLASTIC CTI ABS AS40GF
	PLASTIC CTI NYLON 6/6 NN60CF
	PLASTIC CTI NYLON 6/6 NN60GF
	PLASTIC CTI PEEK PK20CF/000
	PLASTIC CTI POLYSULFONE PF30F/15T
	PLASTIC CTI SAN SN20GF
	PLASTIC CTI SAN SN30GF
	PLASTIC CTI SAN SN40GF
	PLASTIC EPSYN 4506
	PLASTIC ES20GF/000
	PLASTIC ES30CF/000
	PLASTIC ES39GF/000
	PLASTIC ES40GF/000
	PLASTIC ES7CF/000
	PLASTIC NH20GF
	PLASTIC NH30GF
	PLASTIC NH40GF
	PLASTIC NI20GF
	PLASTIC NI30GF
	PLASTIC NI40GF
	PLASTIC NJ30GF
	PLASTIC NL10GF
	PLASTIC NL20GF
	PLASTIC NL30GF
	PLASTIC NL40GF
	PLASTIC NL50GF
	PLASTIC NL60GF
	PLASTIC NN10GF
	PLASTIC NN20CF
	PLASTIC NN20GF
	PLASTIC NN30CF
	PLASTIC NN30GF
	PLASTIC NN40CF
	PLASTIC NN40GF
	PLASTIC NN50GF
	PLASTIC NN60CF1000
	PLASTIC NN60GF
	PLASTIC NY-10GF
	PLASTIC NY-20GF
	PLASTIC NY-30CF
	PLASTIC NY-30GF
	PLASTIC NY-40GF

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
COMPOUNDING TECHNOLOGY (CTI)	PLASTIC NY-50GF
	PLASTIC NY-60GF
	PLASTIC PC-000/10T
	PLASTIC PC-000/15T
	PLASTIC PC-000/20T
	PLASTIC PC-000/5T
	PLASTIC PC-10CF/000
	PLASTIC PC-10GF/000 FR
	PLASTIC PC-20CF
	PLASTIC PC-20CF/15T
	PLASTIC PC-20GF
	PLASTIC PC-20GF/15T
	PLASTIC PC-30CF
	PLASTIC PC-30CF/20
	PLASTIC PC-30GF
	PLASTIC PC-30GF/15T
	PLASTIC PC-40CF
	PLASTIC PC-40GF
	PLASTIC PC-40GF/15T
	PLASTIC PF-000/15T
	PLASTIC PF-10GF/15T
	PLASTIC PF-20GF
	PLASTIC PF-20GF/15T
	PLASTIC PF-30CF
	PLASTIC PF-30GF
	PLASTIC PF-30GF/000
	PLASTIC PF-40GF
	PLASTIC PI 20GF/000
	PLASTIC PI 30GF/000
	PLASTIC PI 40GF/000
	PLASTIC PI-30 CF/000
	PLASTIC PI-40CF/000
	PLASTIC PK-20GF/000
	PLASTIC PK-40CF/000
	PLASTIC PL-20 NCF/000 FCR
	PLASTIC PR-20CF/000
	PLASTIC PS-10GF/000
	PLASTIC PS-15GF/000
	PLASTIC PS-15GF/000 GR
	PLASTIC PS-20GF/000
	PLASTIC PS-30GF 30% GLASS
	PLASTIC PS-30GF/000 FR
	PLASTIC SF-20CF
	PLASTIC SF-20CF/000
	PLASTIC SF-30CF
	PLASTIC SF-30CF/15T
	PLASTIC SF-30GF
	PLASTIC SF-30GF/15T
	PLASTIC SF-40CF
	PLASTIC SF-40GF
CONAIR	COMB STYLING MARK IV
CONAP	ADHESIVE AD10
	ADHESIVE AD15
	ADHESIVE AD16
	ADHESIVE AD3
CONAP	ADHESIVE AD7
	ADHESIVE AD8
	ADHESIVE AD9
	ADHESIVE CONAP AD1146
	ADHESIVE CONAP AD1146-1
	ADHESIVE CONAP AD1146C
	ADHESIVE CONAP AD1146C1
	ADHESIVE CONAP AD1147
	ADHESIVE CONAP AD1147-1
	ADHESIVE CONAP AD1147C
	ADHESIVE CONAP AD1147C1
	ADHESIVE CONAPOXY AD1000
	ADHESIVE CONAPOXY AD1040B/CONACURE EA073A
	ADHESIVE CONAPOXY AD11
	ADHESIVE CONAPOXY AD12
	ADHESIVE CONAPOXY AD13
	ADHESIVE CONAPOXY AD14
	ADHESIVE CONAPOXY AD17
	ADHESIVE CONAPOXY FR1241/EA4
	ADHESIVE CONASTIC 830 OIL/GRIP
	ADHESIVE CONASTIC AD20
	ADHESIVE CONASTIC G1 SERIES
	ADHESIVE CONASTIC ST115
	ADHESIVE EASYPOXY K20
	ADHESIVE EASYPOXY K22
	ADHESIVE EASYPOXY K23A
	ADHESIVE EASYPOXY K256
	ADHESIVE EASYPOXY K26
	ADHESIVE EASYPOXY K40
	ADHESIVE EASYPOXY K45
	ADHESIVE FR1241/EA055
	ADHESIVE K230 B/A
	ADHESIVE STONEPOXY KIT #6-2
	COATING CONAPOXY 1122
	COATING CONATHANE EN2 POLYURETHANE
	COATING CONATHANE EN4 (DPEN6385)
	COATING CONFORMAL CONATHANE CE1155
	POLYURETHANE
	LAMIN EPOXY/GLASS COATED WITH CE1155
	PLASTIC CONAPOXY TE1257/EA071
	PLASTIC CONAPOXY TE1257/EA08
	PLASTIC CONAPOXY TE1257/EA113
	PLASTIC CONAPOXY TE1257/EA116
	PLASTIC CONAPOXY TE1257/EA117
	POTTING COMPOUND CONATHANE DPEN8536
	POTTING COMPOUND CONATHANE EN10
	POTTING COMPOUND CONATHANE EN11
	POTTING COMPOUND CONATHANE EN12
	POTTING COMPOUND CONATHANE EN20
	POTTING COMPOUND CONATHANE EN21
	POTTING COMPOUND CONATHANE EN22
	POTTING COMPOUND CONATHANE EN23
	POTTING COMPOUND CONATHANE EN24
	POTTING COMPOUND CONATHANE EN2523
	POTTING COMPOUND CONATHANE EN2524

MSFC-HDBK-527 REV F 9999942 0006872 8

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
CONAP	POTTING COMPOUND CONATHANE EN2525
	POTTING COMPOUND CONATHANE EN2526
	POTTING COMPOUND CONATHANE EN2527
	POTTING COMPOUND CONATHANE EN2528
	POTTING COMPOUND CONATHANE EN2541
	POTTING COMPOUND CONATHANE EN2543
	POTTING COMPOUND CONATHANE EN2545
	POTTING COMPOUND CONATHANE EN2547
	POTTING COMPOUND CONATHANE EN2548
	POTTING COMPOUND CONATHANE EN30
	POTTING COMPOUND CONATHANE EN5
	POTTING COMPOUND CONATHANE EN6
	POTTING COMPOUND CONATHANE EN7
	POTTING COMPOUND CONATHANE EN8
	POTTING COMPOUND CONATHANE EN9
	POTTING COMPOUND CONATHANE EN9 (OZR)
	POTTING COMPOUND CONATHANE TU400
	POTTING COMPOUND CONATHANE TU4010
	POTTING COMPOUND CONATHANE TU500
	POTTING COMPOUND CONATHANE TU50A
	POTTING COMPOUND CONATHANE TU600
	POTTING COMPOUND CONATHANE TU65A
	POTTING COMPOUND CONATHANE TU700
	POTTING COMPOUND CONATHANE TU79
	POTTING COMPOUND CONATHANE TU80
	POTTING COMPOUND CONATHANE TU800
	POTTING COMPOUND CONATHANE TU89
	POTTING COMPOUND CONATHANE TU900
	POTTING COMPOUND CONATHANE TU955
	POTTING COMPOUND CONATHANE TU960
	POTTING COMPOUND CONATHANE UC17
	POTTING COMPOUND CONATHANE UC21
	POTTING COMPOUND CONATHANE UC22
	POTTING COMPOUND CONATHANE UC23
	POTTING COMPOUND CONATHANE UC24
	POTTING COMPOUND CONATHANE UC25
	POTTING COMPOUND CONATHANE UC26
	POTTING COMPOUND CONATHANE UC27
	POTTING COMPOUND CONATHANE UC30
	POTTING COMPOUND CONATHANE UC31
	POTTING COMPOUND CONATHANE UC32
	POTTING COMPOUND CONATHANE UC33
	POTTING COMPOUND CONATHANE UC34
	POTTING COMPOUND CONATHANE UF3
	POTTING COMPOUND EASYPOXY K230
CONMED	ADHESIVE CONDUCTIVE VERSATAC PAD
CONN HARD RUBBER	FABRIC FIBERGLASS/VITON 5707
	FABRIC GLASS/SILICONE
	FABRIC NOMEX/VITON 5713
	FABRIC NYLON SILICONE COATED 1409
	FABRIC POLYAMIDE TYPE ASI
	FABRIC SILICONE 1 GLASS
	FABRIC SILICONE/GLASS 3010
	FABRIC SILICONE/GLASS 3016
	RUBBER COHRLASTIC 10480 SILICONE

MANUFACTURER	DESIGNATION
CONN HARD RUBBER	RUBBER COHRLASTIC 300
	RUBBER COHRLASTIC 3111 GLASS REINFORCED
	SILICONE FILM
	RUBBER COHRLASTIC 400
	RUBBER COHRLASTIC 4032 GLASS REINFORCED
	SILICONE SHEET
	RUBBER COHRLASTIC 4050 SILICONE GLASS
	RUBBER COHRLASTIC 4150 SILICONE/GLASS
	RUBBER COHRLASTIC 500
	RUBBER COHRLASTIC 600
	RUBBER COHRLASTIC 700 SILICONE
	RUBBER COHRLASTIC 9030
	RUBBER COHRLASTIC 9040
	RUBBER COHRLASTIC 9050
	RUBBER COHRLASTIC 9070
	RUBBER COHRLASTIC 9235
	RUBBER COHRLASTIC 9255
	RUBBER COHRLASTIC 9275
	RUBBER COHRLASTIC 9750
	RUBBER COHRLASTIC 9770
	RUBBER COHRLASTIC 9855
	RUBBER COHRLASTIC R10450
	RUBBER COHRLASTIC R10460 SILICONE
	RUBBER COHRLASTIC R10470 SILICONE
	RUBBER COHRLASTIC X4052 GLASS REINFORCED
	SILICONE SHEET
	RUBBER SILICONE 200A
	RUBBER SILICONE HARDNESS SHORE "A" 35-45
	RUBBER SILICONE NOC ZZ-R-765
	RUBBER VITON V80-080/CHR 985
	SPONGE RUBBER SILICONE
	TAPE C666
	TAPE G550 FIBERGLASS/ACRYLIC
	TAPE KAPTON K107 GOLD REINFORCED
	TAPE KAPTON/ACRYLIC K109
	TAPE KAPTON/GLASS/SILICONE JE4.10
	TAPE KAPTON/SILICONE K350 PS
	TAPE MYLAR M69 WITH ACRYLIC ADHESIVE
	TAPE POLYIMIDE/SILICONE K100
	TAPE STICK AND STRIP 10470 SILICONE
	TAPE TEFLON FEP WITH Y966 TRANSFER
	ADHESIVE
	TAPE TEFLON/SILICONE
	TAPE TEMP-R-GLASS A2008
	TAPE TEMP-R-TAPE C
	TAPE TEMP-R-TAPE G569
	TAPE TEMP-R-TAPE HM350 TFE/SIL
	TAPE TEMP-R-TAPE HM430
	TAPE TEMP-R-TAPE HM50
	TAPE TEMP-R-TAPE K102R
	TAPE TEMP-R-TAPE K250
	TAPE TEMP-R-TAPE K350SP
	TAPE TEMP-R-TAPE ON TEDLAR FILM
	TAPE TEMP-R-TAPE T155
	TAPE TEMP-R-TAPE TV350

MSFC-HDBK-527 REV F 9999942 0006873 T

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
CONQUEST SEAL CORP	RUBBER VITON FLUID RESISTANT
CONRAC	WIRE ELEC FLEXIBLE PRINTED/KAPTON
CONRAD INDUSTRIES	EMBLEM CLOTH SHUTTLE
CONSOLIDATED CONTROLS	KEL-F CTFE UNPLASTICIZED
	TEFLON PTFE DISCS
	WIRE ELEC SAMPLES V6.N22-9
CONSOLIDATED KINETIC	ADHESIVE 76/KUA FOAM
	INSULATION FOAM KUA/ARMALON/CSR300 ADHES
	INSULATION FOAM KUA/BLACK VINYL COVER
	INSULATION FOAM KUA100
	INSULATION FOAM URETH KUA100/FLUOREL COATED
	INSULATION FOAM URETHANE KUA
	INSULATION FOAM URETHANE KUA100U-7LF
	INSULATION FOAM URETHANE KUA50-7LF
CONTINENTAL POLYMERS INC	PLASTIC CP41
	PLASTIC CP51
	PLASTIC CP61
	PLASTIC CP80
	PLASTIC CP81
	PLASTIC CP82
CONTRAVES	ANTENNA MATL KEV/KAP/EPOXY
CONVAIR	LAMIN EPOXY/GRAPHITE/KEVLAR
CONVERSE	SHOE TENNIS NYLON/RUBBER
COOK BELTING CO	RUBBER KR2001
	RUBBER KR2006
	RUBBER KR2501
	RUBBER KR2502
	RUBBER KR2503
	RUBBER KR2504
	RUBBER KR2601
	RUBBER KR2602
	RUBBER KR2603
	RUBBER KR2604
	RUBBER KR2605
	RUBBER KR2606
	RUBBER KR2621
	RUBBER KR2622
	RUBBER KR2623
	RUBBER KR3001
	RUBBER KR3002
	RUBBER KR3003
	RUBBER KR3004
	RUBBER KR3502
	RUBBER KR3503
	RUBBER KR3504
	RUBBER KR3601
	RUBBER KR3602
	RUBBER KR3603
	RUBBER KR3604
	RUBBER KR3605
	RUBBER KR3606
	RUBBER KR3621
	RUBBER KR3622
	RUBBER KR3623

MANUFACTURER	DESIGNATION
COOK BELTING CO	RUBBER KR4002
	RUBBER KR4003
	RUBBER KR4004
	RUBBER KR5002
	RUBBER KR5003
	RUBBER KR5004
	RUBBER KR9002
	RUBBER NITRILE GRADE 30
	RUBBER NITRILE GRADE 40
	RUBBER NITRILE GRADE 50
	RUBBER NITRILE GRADE 60
	RUBBER NITRILE GRADE 70
	RUBBER NITRILE GRADE 80
COOK PAINT & VARNISH	COATING NEXTEL 900 WHITE
	INSULATION FOAM 402 POLYURETHANE
	INSULATION FOAM POLYURETHANE 711
COOLEY INC	FABRIC NYLON/PVC TXN266
	FABRIC POLYESTER/PVS L-109 KUP
COONER WIRE CO	CABLE ELEC COONER AS155-28-2SJ
COOPER GROUP	SOLIDOX TYPE "B" IGNITER
COORS PORCELAIN	CERAMIC AD995 ALUMINA (INORG)
	CERAMIC ALUMINA AD-96
	CERAMIC ALUMINO-SILICAT P1/2BC
COPOLYMER RUBBER AND CHEM CORP	PLASTIC COPO 1507
	PLASTIC EPSYN 2506
	PLASTIC EPSYN 40A
	PLASTIC EPSYN 4906
	PLASTIC EPSYN 5508
	PLASTIC EPSYN 70A
	PLASTIC EPSYN 7506
	PLASTIC NYSYN 28-7XL
CORNING GLASS WORKS	GLASS BOROSILICATE (INORGANIC)
CORTLAND LINE	CORD DACRON BRAIDED TROLL 70LB
	CORD KEVLAR 29 B/B 16X15
	CORD KEVLAR BB2912 30/12X30
COSDEN OIL & CHEMICAL CO	PLASTIC COSDEN 500
	PLASTIC COSDEN 525
	PLASTIC COSDEN 535
	PLASTIC COSDEN 550
	PLASTIC COSDEN 560
	PLASTIC COSDEN 625
	PLASTIC COSDEN 680
	PLASTIC COSDEN 740
	PLASTIC COSDEN 825
	PLASTIC COSDEN 825E
	PLASTIC COSDEN 945
COSMIC PLASTICS	MOLD COMPOUND DAP DC-62
	PLASTIC 224
	PLASTIC 306
	PLASTIC D33
	PLASTIC D44
	PLASTIC D45
	PLASTIC D62
	PLASTIC D62CM
	PLASTIC D63

MSFC-HDBK-527 REV F 9999942 0006874 1

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
COSMIC PLASTICS	PLASTIC D69
	PLASTIC D72
	PLASTIC D73
	PLASTIC D73F
	PLASTIC E484
	PLASTIC E486
	PLASTIC E487
	PLASTIC E4905
	PLASTIC E4920
	PLASTIC E4930
	PLASTIC K31
	PLASTIC K43
	PLASTIC K61
	PLASTIC K66
	PLASTIC K77
COTTON INC	FABRIC 100% COTTON FR 7 OZ BLUE
	FABRIC BASE-TREATED COTTON AMMONIA CURE WITH NASA TOPPING (DRY-CLEANED)
	FABRIC BASE-TREATED COTTON AMMONIA CURE WITH NASA TOPPING (WASHED/DRIED 25 TIMES)
	FABRIC COTTON 100%(FR/2%THPOH)
	FABRIC COTTON AIRC84410-502/FR
	FABRIC COTTON BLUE MOUNTAIN
	FABRIC COTTON DUCKWEAVE FR
	FABRIC COTTON FLAME RETARD 4 OZ
	FABRIC COTTON FLAME RETARDANT
	FABRIC COTTON RED
	FABRIC COTTON S55 F/PNH3 D/F
	FABRIC COTTON S65 F/PNH3 D/F
	FABRIC COTTON SHIRTING MC PP1
	FABRIC COTTON SHIRTING/TOPSOFT
	FABRIC COTTON SLEEP RESTRAINT
	FABRIC COTTON TWILL
	FABRIC COTTON TWILL GRT8134
	FABRIC COTTON TWILL SHIRTING
	FABRIC COTTON WESTEX SATINE
	FABRIC COTTON WESTEX TWILL
	FABRIC COTTON/DCY JERSEY KNIT
	FABRIC SATEEN COTTON 4OZ/YD
	FABRIC SATEEN EX 1B HC 6.9 OZ
	FABRIC TWILL EX 3A 1.93 6.9 OZ
COX & CO	POTTING COMPOUND COX 28 EPOXY
	POTTING COMPOUND COX 4021/4036
	RUBBER FLUOREL 4500
	TUBING SILICONE SR200 #18
	TUBING SILICONE SR200 16
	WIRE HEATER MC363-0031 0038
CPR DIVISION	INSULATION FOAM CPR306-2/REFSET COATED
CRAIG CORP	RECORDER AUDIO 2625
CRANE PACKING CO	PLASTIC 10% CARBON-GRAPHITE/90% TFE
	PLASTIC 12.5% GLASS FIBER/12.5% MOS2/75% TFE
	PLASTIC 15% GLASS FIBER/5%MOS2/80% TFE
	PLASTIC 25% CARBON-GRAPHITE/75% TFE
	PLASTIC 35% CARBON-GRAPHITE/65% TFE
CRANE PACKING CO	PLASTIC 40% BRONZE/5% MOS2/55% TFE
	PLASTIC 40% BRONZE/60% TFE
	PLASTIC 5% GLASS FIBER/5%MOS2/75% TFE
	PLASTIC 5% GLASS FIBER/95% TFE
	PLASTIC 60% BRONZE/40% TFE
	PLASTIC 70% BRONZE/30% TFE
	PLASTIC BRONZE/5% MOS2/40% TFE
	TEFLON TFE VIRGIN
CREAVEY SEAL CO	TUBING VIRGIN FEP TEFLON
CREST PRODUCTS	ADHESIVE CREST 1013 A/B
	ADHESIVE CREST 141 A/B
	ADHESIVE CREST 170
	ADHESIVE CREST 173 A/B
	ADHESIVE CREST 2027 A/B
	ADHESIVE CREST 2053 A/B
	ADHESIVE CREST 2079 A/B
	ADHESIVE CREST 2092 A/B
	ADHESIVE CREST 2154 A/B
	ADHESIVE CREST 2800 A/B
	ADHESIVE CREST 3119 A/B
	ADHESIVE CREST 3120 A/B
	ADHESIVE CREST 3133 A/B
	ADHESIVE CREST 3135 A/B
	ADHESIVE CREST 3144 A/B
	ADHESIVE CREST 3147 A/B
	ADHESIVE CREST 3170 A/B
	ADHESIVE CREST 3181
	ADHESIVE CREST 391 A/B
	ADHESIVE CREST 4096 A/B
	ADHESIVE CREST 627
	ADHESIVE CREST 642 A/B
	ADHESIVE CREST 723 A/B
	ADHESIVE CREST 7344 A/B
	ADHESIVE CREST 7450 POLYURETHANE
	ADHESIVE CREST 760 A/B
	ADHESIVE CREST 800 A/B
	ADHESIVE CREST 805 A/B
	ADHESIVE CREST 837
	ADHESIVE CRYOSEAL 2132
	ADHESIVE CRYOSEAL 605
	INSULATION FOAM CREST 2460
	INSULATION FOAM CREST 3030 TAN
	INSULATION FOAM CREST 7530 TAN
	INSULATION FOAM URETHANE J52924
CRITON CORP	CLAMP SILICONE/GLASS
CROAKIES	STRAP EYEGLASS RETENTION
CROFTON INC	INSULATION FOAM OMALON 3
CROMPTON HIGHLANDS	FABRIC VELVETEEN
CROSBY VALVE CORP	TEFLON TFE/25% GLASS
CROWN ZELLERBACH	TISSUE TOILET SINGLEFOLD
CRUMBACHER	BRUSH AL/WOOD/CAMEL HAIR
CULLERY CHEMICAL CO	INSULATION FOAM POLYURETHANE FS110 MMC
CURBELL	PLASTIC POLYPENCO 25% GLASS FILLED TFE
	PLASTIC POLYPENCO FLUOROSINT 207
	PLASTIC POLYPENCO FLUOROSINT 500

MSFC-HDBK-527 REV F 9999942 0006875 3

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
CURBELL	PLASTIC POLYPENCO TFE FLUOROCARBON
	PLASTIC TFE FLUOROCARBON
CURTIN MATHESON	GLOVE PVC DISPOSABLE
CUSTOM MATERIALS INC	VELOSTAT 2.5 MIL
CUSTOM PACKING	ADHESIVE 76/URETHANE FOAM
	INSULATION FOAM FLUOREL/URETHANE COATED
	INSULATION FOAM PYRELL LS645CZ
CUSTOM RESINS	PLASTIC NYLON 401
	PLASTIC NYLON 402
	PLASTIC NYLON 404
	PLASTIC NYLON 406
	PLASTIC NYLON 409
	PLASTIC NYLON 451
	PLASTIC NYLON 452
	PLASTIC NYLON 453
	PLASTIC NYLON 454
	PLASTIC NYLON 600
	PLASTIC NYLON 601
	PLASTIC NYLON 603
	PLASTIC NYLON 607
	PLASTIC NYLON 609
	PLASTIC NYLON 615
	PLASTIC NYLON NX 2011
	PLASTIC NYLON NX 5703
	PLASTIC NYLON NX 6200
CUTTERS EXCHANGE	LEAD TAXCHEM MARKING 200 BLUE
	LEAD TAXCHEM MARKING 200 GREEN
	POWDER 8804 STAMPING BLUE
CY/RO INDUSTRIES	PLASTIC EXOLITE DOUBLE SKINNED ACRYLIC SHEET
	PLASTIC EXOLITE DOUBLE SKINNED POLYCARBONATE SHEET
D AIRCRAFT PRODUCTS	ADHESIVE DAPCOTAC 3008 EPOXY
	COATING DAPCO 2031 FLUOROELASTOMER
	COATING DAPCOTAC 3300TH ADHESIVE
	INSULATION FOAM PDL4034-2.5/COVERED WITH L-T-80 TAPE/SEALED WITH DAPCO 2030
	RUBBER SILICONE SMC1050
	SEALANT NEOPRENE DAPCO 2030
DAIKIN KOGYO CO	COATING POLYFLON SPRAY WAX
DAINICHI NIHON DENSHI CO	RUBBER VITON 840627 (1320-75)
DAINIPPON INK	ADHESIVE EPOXY RESIN RE103
	INSULATION POLYIMIDE/GLASS RI409/SLS21
	INSULATION THERMAL RI409/SLS 213B NOMEX
	LAMIN POLYIMIDE/GLASS
DALE MANUFACTURING	CONNECTOR RECTANGULAR RACK AND PANEL P/N MM22G5-44SK2H AND P/N MMDIP2265-44SL2L
DAP INC	ADHESIVE DAP
	COATING DERUSTO 511 EPOXY WHITE
	COATING INDOTHANE 441-1C-41 WHITE
DARLINGTON FABRICS	FABRIC LYCRA SPANDEX
	FABRIC MULTI FIL G1106-80MZL
	FABRIC SPANDEX NYLON
DART INDUSTRIES	CONNECTOR PIN MUPAC 108/NYLAFIL G20/40
DART INDUSTRIES	LAMIN ACRYLACON/FIBERGLASS RNF
	MOLD COMPOUND NYAFIL G10/40
	PLASTIC PS102-0
	PLASTIC PS102-1
	PLASTIC PS108-1
	PLASTIC PS118-1
	PLASTIC PS202
	PLASTIC PS208
	PLASTIC PS304
	PLASTIC PS308
DATEL	CONNECTOR P/N 2075060
	CONNECTOR TAPE RECORDER
	POWER SUPPLY UPM15/100 ASSEMBLY
DAVID CLARK	DUCT VENT ASSEMBLY
	FABRIC FYPRO
	FABRIC FYPRO 9805 P46EH
	FABRIC FYPRO TREATED NOMEX
	HELMET FLIGHT ANTI-G
	LEATHER NAME PATCHES
DAVIS INTERNATIONAL	INSULATION FOAM CPR9700-1.75 POLYURETHANE
DAYCO CORP	HOSE FLEX DURAVENT U8 CLEAR
	HOSE TEMPFLEX PLUS BLACK
DAYGLO COLOR CORP	INK S66-13 ROCKET RED
	INK S66-16 ARC YELLOW
	INK S66-17 SATURN YELLOW
	INK S66-18 SIGNAL GREEN
DAYTON PRODUCTS	ADHESIVE THIXON 300/301
	ADHESIVE THIXON 305
	ADHESIVE THIXON 409
	ADHESIVE THIXON 416
	ADHESIVE THIXON 508
	ADHESIVE THIXON 511T
	ADHESIVE THIXON 711
	ADHESIVE THIXON 752
	ADHESIVE THIXON 803-1
	ADHESIVE THIXON 806 (AP1442)
	ADHESIVE THIXON 807 (AP1559) NEOPRENE
	ADHESIVE THIXON 814-1
	ADHESIVE THIXON 925
	ADHESIVE THIXON 926
	ADHESIVE THIXON 927
	ADHESIVE THIXON 936
	ADHESIVE THIXON 942
	ADHESIVE THIXON 943
	ADHESIVE THIXON 954
	ADHESIVE THIXON AP3395
	ADHESIVE THIXON GPO
	ADHESIVE THIXON OSN2
	ADHESIVE THIXON P10
	ADHESIVE THIXON P6-1
	ADHESIVE THIXON P7
	COATING PHENOLIC P-5 PRIMER
	MOLD COMPOUND NYLATRON MOS2 FILLED
	RUBBER LATEX GLOVES
DE WAL IND	TAPE DW204 TFE/SILICONE

MSFC-HDBK-527 REV F 9999942 0006876 5

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
DE WAL IND	TAPE TEFLON FLUOROLIN 101 WITH PS SILICONE ADHESIVE
DEANCO	TUBING TEFLON TFE ZEUS 14 HST
DEARBORN WIRE & CABLE	TUBING PTFE SHRINKABLE
DEARCOM WIRE & CABLE	CABLE COAX RG142 PTFE CORE FEP JACKET SILVER COATED COPPER
	CABLE COAX RG188
DEERFIELD MFG CO	FILM POLYURETHANE 10 MIL
	FILM POLYURETHANE 5 MIL
DEFENSE DEPOT	CONNECTOR ELECTRICAL PLUG
DEFT	COATING 02-GY-3 EPOXY
	COATING 02-GY-3 WITH ARAMID LAMIN
	COATING 023-GW-3/CHEMGLAZE A276 P
	COATING 03-BK-28 WITH CATALYST
	COATING 03-BK-29 POLYURETHANE FLAT BLACK
	COATING 03-BK-29 PRIMER
	COATING 03-BL-51 POLYURETHANE FLAT BLUE
	COATING 03-GY-62 FLAT LIGHT GRAY TOX RATE STUDY
	COATING 03-GY-62 GRAY OVER MB0125-055 PRIMER
	COATING 03-GY-62 POLYURETHANE FLAT LIGHT GRAY
	COATING 03-W-40 POLYURETHANE GLOSS WHITE
	COATING 03-Y-30 PRIMER
	COATING 44 GM-7 AIRCRAFT
	COATING 44-GN-11 EPOXY POLYAMIDE
	COATING 44-GN-11/CHEMGLAZE A276
	COATING A276/02-Y-24
	COATING CHEMGLAZE A276/02-GN-40 PRIMER
	COATING CHEMGLAZE Z302/02-GN-40PRIMER
	COATING CHEMGLAZE Z306/02-GN-40 PRIMER
	COATING DEPTHANE GLOSS #1 POLYURETHANE
	COATING EPOXY/POLYIMIDE
	COATING POLYAMIDE EPOXY
	COATING POLYIMIDE BLACK 37038 EPOXY
	COATING POLYURETHANE BLACK
	COATING POLYURETHANE LT GRAY 36622
	COATING POLYURETHANE WHITE
	COATING POLYURETHANE YELLOW 23785
	COATING POLYURETHANE YELLOW 33538
	COATING POLYURETHANE YELLOW/SUPER KOROPON
	COATING PRIMER/CHEMGLAZE A276
	COATING URETHANE 03W127
	COATING WATER BASE PRIMER
	INK WARNOWINK M-9-N WITH DEPTHANE GLOSS NO. 1 OVERCOAT
	LAMIN DUCT 02GY3 TC URETHANE 17875
	LAMIN EPOXY/GLASS STRUCOL R1602
	SEALANT EPOXY CORROSION INHIBITOR 71-Y-1
DEHNER CO	BOOT 05078 LEATHER/NYLON
DEKEM CO	INK KX425 BLACK
DELTA ELASTIC CO	FABRIC ELASTIC 733 1.25 WIDE
DENKI KAGAKU KOGYO CO	ADHESIVE THERMAL CONDUCTIVE A140 FR R1
DENNIS CHEMICAL	ADHESIVE M6704 EPOXY

MANUFACTURER	DESIGNATION
DENNIS CHEMICAL	COATING DENNIS 1169 URETHANE A/B
DENNISON MFG	ADHESIVE DENNISON A30
	ADHESIVE DENNISON A40
	ADHESIVE DENNISON A52
	ADHESIVE DENNISON A53
	ADHESIVE DENNISON A70
	ADHESIVE DENNISON A72
	ADHESIVE DENNISON A73
	ADHESIVE DENNISON C21
	ADHESIVE DENNISON C37
	ADHESIVE DENNISON GLUE STIC
	ADHESIVE DENNISON M11
	ADHESIVE DENNISON M12
	ADHESIVE DENNISON M58
	ADHESIVE DENNISON M9
	ADHESIVE DENSIL SILICONE PS
	FASTENER DENISON
DESOTO	COATING 03-BK-29 POLYURETHANE FLAT BLACK
	COATING 03-GY-62 POLYURETHANE FLAT LIGHT GRAY
	COATING 17875 POLYURETHANE WHITE
	COATING 4367-3 ON LAMIN 515-700
	COATING 463-3-33 TC/515-700 PRIMER
	COATING 513-703/821-331/910-736
	COATING 513X332/910X457 PRIMER
	COATING 515-700/910-704 463-3-100/118
	COATING 515-700/910-704 CATALYST
	COATING 515-703/910-736 PRIMER
	COATING 515X346 EPOXY
	COATING 528-305/515-700 PRIMER
	COATING 529-001/910-037/020-004
	COATING 821-331 POLYURETHANE FLAT WHITE
	COATING 821-331 POLYURETHANE FLAT WHITE WITH PRIMER
	COATING 821-400 POLYURETHANE GLOSS WHITE
	COATING 821-425/515-700 PRIMER
	COATING 822-326 PRIMER
	COATING 822-327 GRAY 36231 OVER MB0125-055 PRIMER
	COATING 822-327 POLYURETHANE FLAT GRAY
	COATING 822-327 POLYURETHANE FLAT LT GRAY
	COATING 823-311 POLYURETHANE FLUOREL/ YELLOW
	COATING 823-311 PRIMER
	COATING 823-363 POLYURETHANE GLOSS ORANGE
	COATING 824-408 POLYURETHANE GLOSS ORANGE
	COATING 828-310 FLAT BLACK TOX RATE STUDY
	COATING 828-310 POLYURETHANE FLAT BLACK
	COATING 828-310 PRIMER
	COATING CHEMGLAZE A276/KOROPON
	COATING F/N-65208 PRIMER EPOXY
	COATING F/N-6620F EPOXY
	COATING KOROPON SUPER HI TEMP
	COATING PAINT YELLOW 33798 URETHANE/PRIMER EPOXY AMIDE

MSFC-HDBK-527 REV F 9999942 0006877 7

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
DESOTO	COATING POLYAMIDE EPOXY
	COATING POLYURETHANE TOPCOAT #1
	COATING POLYURETHANE TOPCOAT #2
	COATING POLYURETHANE TOPCOAT #3
	COATING POLYURETHANE YELLOW/SUPER KOROPON
	COATING S13-707 EPOXY
	COATING SUPER KOROPON 515-700
	COATING SUPER KOROPON/LATEX433495
DESOTO/ADVANCED PROD	COATING PAINT YELLOW 33798 URETHANE/PRIMER EPOXY AMIDE
DETREX CHEMICAL	COATING ACCUMETRIC A105
DEUTSCH	ADHESIVE ELASTOMERIC PROPRIETARY
	CONNECTOR 38108-24-61S
	CONNECTOR DM5623-37-37 PP
	CONNECTOR ELEC DG123
	CONNECTOR ELECTRIC
	CONNECTOR ELECTRIC 84450
	CONNECTOR ELECTRICAL
	CONNECTOR JUNCTN CTV122E05/10
	CONNECTOR SILICONE/RUBBER 40S
	INK DEUTSCH DPS CL 1,3,4,5
	INK DEUTSCH DPS I140-01 MARKNG
	INK DEUTSCH DPS147
	INK DEUTSCH DPS300
	RUBBER SILICONE 405
	RUBBER SILICONE DMCPS1008
	TEFLON TFE VIRGIN
DEVCON CORP	ADHESIVE DEVCON 2-TON EPOXY WHITE
	ADHESIVE DEVCON 5-MINUTE EPOXY
	ADHESIVE DEVCON 5-MINUTE EPOXY GEL
	ADHESIVE DEVCON ALUMINUM LIQUID 10710
	ADHESIVE DEVCON ALUMINUM PUTTY
	ADHESIVE DEVCON ALUMINUM VERY LIQUID 11720
	ADHESIVE DEVCON BACKING COMPOUND LIQUID 11915
	ADHESIVE DEVCON BRONZE PUTTY 10260
	ADHESIVE DEVCON BRUSHABLE CERAMIC COMPOUND 11760
	ADHESIVE DEVCON CARBIDE PUTTY 10050
	ADHESIVE DEVCON CERAMIC WEAR COMPOUND 11680
	ADHESIVE DEVCON DK40
	ADHESIVE DEVCON EK1
	ADHESIVE DEVCON EPOXY SEALER 100
	ADHESIVE DEVCON FLOOR GRIP 13090
	ADHESIVE DEVCON FLOOR PATCH 13100
	ADHESIVE DEVCON H-TEMP CERAMIC PUTTY 11690
	ADHESIVE DEVCON HI-TEMP MOLD MAKER 10370
	ADHESIVE DEVCON LOCK-STUD LOCKING GRADE 19530
	ADHESIVE DEVCON LOCK-THREAD LOCKING PENETRANT-SUPER 18560
	ADHESIVE DEVCON MVP TYPE II
	ADHESIVE DEVCON PLASTIC/STEEL 5-MINUTE PUTTY

MANUFACTURER	DESIGNATION
DEVCON CORP	ADHESIVE DEVCON PLASTIC/STEEL LIQUID 10210
	ADHESIVE DEVCON PLASTIC/STEEL PUTTY 10110
	ADHESIVE DEVCON PUMP REPAIR PUTTY 11700
	ADHESIVE DEVCON RUBBER 14900
	ADHESIVE DEVCON SPECIAL F EPOXY
	ADHESIVE DEVCON ST EPOXY
	ADHESIVE DEVCON STAINLESS STEEL PUTTY 10270
	ADHESIVE DEVCON SUPER LOCK-NUT LOCKING GRADE 18520
	ADHESIVE DEVCON SUPER LOCK-RETAINING GRADE 18540
	ADHESIVE DEVCON TILE ADHESIVE
	ADHESIVE DEVCON TITANIUM PUTTY
	ADHESIVE DEVCON WET SURFACE REPAIR PUTTY 11800
	ADHESIVE METHACRYLATE MX611
	ADHESIVE MVP TY 33
	ADHESIVE SILITE RTV HI-TEMP SILICONE
	ADHESIVE SILITE RTV SILICONE
	ADHESIVE TANKITE 2
	ADHESIVE ZIPGRIP 10
	ADHESIVE ZIPGRIP 100
	ADHESIVE ZIPGRIP 1500
	ADHESIVE ZIPGRIP 5
	ADHESIVE ZIPGRIP 50
	ADHESIVE ZIPGRIP SUPER GLUE
	DEVCON SUPER LOCK-SCREW LOCKING GRADE 18510
	PLASTIC ALUMINUM LIQUID
	PLASTIC ALUMINUM PUTTY
	PLASTIC ALUMINUM VERY LIQUID
	PLASTIC BRONZE PUTTY
	PLASTIC BRUSHABLE CERAMIC COMPOUND
	PLASTIC CARBIDE PUTTY
	PLASTIC CERAMIC WEAR COMPOUND
	PLASTIC DEVCON WET SURFACE REPAIR PUTTY
	PLASTIC EK40
	PLASTIC FLEXANE 80 LIQUID
	PLASTIC FLEXANE 94 LIQUID
	PLASTIC FLEXANE BRUSHABLE URETHANE
	PLASTIC FLEXANE HIGH PERFORMANCE PUTTY
	PLASTIC FLEXANE PUTTY
	PLASTIC FLOOR GRIP
	PLASTIC FLOOR PATCH
	PLASTIC HIGH TEMP CERAMIC PUTTY
	PLASTIC HIGH TEMP MOLD MAKER
	PLASTIC PLASTIC STEEL PUTTY
	PLASTIC PLUMB REPAIR PUTTY
	PLASTIC STAINLESS STEEL PUTTY
	PLASTIC STEEL 5-MIN. PUTTY
	PLASTIC STEEL LIQUID
	PLASTIC TANKITE II
	PLASTIC TITANIUM PUTTY
	PLASTIC WEAR RESISTANT LIQUID

MSFC-HDBK-527 REV F 9999942 0006878 9

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
DEVCON CORP	PLASTIC WEAR RESISTANT PUTTY
	PLASTIC WET SURFACE REPAIR PUTTY
DEVON	ADHESIVE SILICONE SILITE 17150
	FILM VINYL CLEAR UNPLASTICIZED WITH RUBBER
	RESIN ADHESIVE SYSTEM 14T-SS
DIAB-BARRACUDA	INSULATION FOAM DIVINYCELL HT-50
DIAL INDUSTRIES	ANTI-PERSPIRANT DIAL UNSCENTED
	DEODORANT DIAL SOLID
DIALIGHT	LED DISPLAY
DIAPHRAGM INDUSTRIES	DIAPHRAGM SILICONE/NOMEX
	FABRIC DACRON WITH RUBBER BUTYL
DICRONITE	LUBE DRY DICRONITE DL5
DIELECTRIC POLYMERS	PLASTIC 1D30HIF
	PLASTIC 1D40
	PLASTIC 1D50
	PLASTIC 2S30
	PLASTIC 3D36
	PLASTIC DIELECTRITE 44 DR-UL BMC
	PLASTIC DIELECTRITE 44-0
	PLASTIC DIELECTRITE 44-1 BMC
	PLASTIC DIELECTRITE 44-10 BMC
	PLASTIC DIELECTRITE 44-10 HG
	PLASTIC DIELECTRITE 44-10 HG-C
	PLASTIC DIELECTRITE 44-22 BMC
	PLASTIC DIELECTRITE 46-09 BMC
	PLASTIC DIELECTRITE 46-12 BMC
	PLASTIC DIELECTRITE 46-14
	PLASTIC DIELECTRITE 46-16 BMC
	PLASTIC DIELECTRITE 46-3 BMC
	PLASTIC DIELECTRITE 48-50 BMC
	PLASTIC DIELECTRITE 48-56 BMC
	PLASTIC E7052
	PLASTIC E7074
	PLASTIC EM7302
	PLASTIC INSULSTRUC P1001FR BMC
	PLASTIC INSULSTRUC P5000GP
	PLASTIC INSULSTRUC P5003FR
	PLASTIC M4135
	PLASTIC POLYDAP 6120
	PLASTIC POLYDAP 6120F
	PLASTIC POLYDAP 6130
	PLASTIC POLYDAP 6130F
	PLASTIC POLYDAP 6160
	PLASTIC POLYDAP 6220
	PLASTIC POLYDAP 6260
	TAPE NELTAPE 100 TRANSFER
	TAPE NELTAPE 410 TRANSFER
DIGITRAN	MINISWITCH N7-L-438
	MINISWITCHES
DIKE-O-SEAL	RUBBER ABRASHUN 5015
	RUBBER ABRASHUN 5035
	RUBBER ABRASHUN 5040
	RUBBER ABRASHUN 5045
	RUBBER ABRASHUN 5055
	RUBBER ABRASHUN 5065
DIKE-O-SEAL	RUBBER ABRASHUN 5075
	RUBBER ABRASHUN 5088
	RUBBER ABRASHUN 5095
	RUBBER ABRASHUN 5097
	RUBBER ABRASHUN 5098
DIMITER EMULSION & CHEMICAL	ADHESIVE A R A
	ADHESIVE CONTACT 1001
	ADHESIVE E39
	ADHESIVE E41
	ADHESIVE EMBOND 747
	ADHESIVE EMPLAST 560
	ADHESIVE M P A MARK II
	ADHESIVE M P A MARK II 1087
	ADHESIVE M P A MARK II 1095
	ADHESIVE M90
DINNISON	LABELS PRES-A-PLY REMOVABLE
DIVERSIFIED CHEM	COATING DCI SYSTEM 20 POLYMER
DIXICO	BAG POLYETHYLENE RCAS 1200
DIXIE CLAY	FABRIC NYLON/VITON
	RUBBER VITON
DIXON INDUSTRIES	MARKING CRAYON 900 GRAPHITE BLK
	MARKING CRAYON 900 YELLOW
	MARKING CRAYON 904 CARBON BLK
	PLASTIC 15% CARBON, PTFE
	PLASTIC 20% GLASS, 5% MOS2, PTFE
	PLASTIC ACETAL 10% GLASS
	PLASTIC ACETAL 20% GLASS
	PLASTIC ACETAL 21% TFE
	PLASTIC COMPOUND 954
	PLASTIC DIXON 20% GLASS 5% GRAPHITE
	PLASTIC DIXON 55% BRONZE 5% MOS2
	PLASTIC DIXON 60% BRONZE
	PLASTIC DIXON COMPOUND 201 PTFE
	PLASTIC DIXON COMPOUND 7035 PTFE
	PLASTIC DIXON NYLON 6/6 40% CF
	PLASTIC MELOIN 9000
	PLASTIC MELOIN P1 POLYIMIDE
	PLASTIC MELOIN P1-15Y POLYIMIDE
	PLASTIC MELOIN P1-30X POLYIMIDE
	PLASTIC NYLON 6
	PLASTIC NYLON 6.6 30% CF 15% TFE
	PLASTIC NYLON 6.6 33% GLASS
	PLASTIC NYLON 6/6 10% GLASS
	PLASTIC NYLON 6/6 MINERAL FILLED
	PLASTIC PBT (RYNITE)
	PLASTIC PEEK
	PLASTIC PENNLON UHMWPE
	PLASTIC POLYCARBONATE
	PLASTIC POLYCARBONATE 20% GLASS
	PLASTIC POLYETHERSULFONE 30% CF
	PLASTIC POLYETHERSULFONE 30% GLASS
	PLASTIC POLYPROPYLENE
	PLASTIC POLYPROPYLENE 10% GLASS
	PLASTIC POLYPROPYLENE 30% GLASS
	PLASTIC POLYSULFONE

MSFC-HDBK-527 REV F 9999942 0006879 0

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
DIXON INDUSTRIES	PLASTIC POLYSULFONE 30% CF
	PLASTIC PPO
	PLASTIC PVDF
	PLASTIC RULON 123, PTFE
	PLASTIC RULON A TFE/GLASS
	PLASTIC RULON E, PTFE
	PLASTIC RULON G-65, PTFE
	PLASTIC RULON II
	PLASTIC RULON J TFE/GLASS
	PLASTIC RULON J, PTFE
	PLASTIC RULON LD, PTFE
	PLASTIC RULON LOP-A, PTFE
	PLASTIC RULON W-2, PTFE
	PLASTIC RYTON 15% TFE 30% CF
	PLASTIC RYTON R-8
	PLASTIC TORLON 5030
	PLASTIC TROGAMID
	PLASTIC ULTEM 2100
	PLASTIC ULTEM 2200
	PLASTIC ULTEM 2300
	TEFLON TFE VIRGIN
	TUBING ELEC PTFE HST DUAL WALL
	TUBING POLYOLEFIN DUAL WALL HST
DODGE	COATING XECOTE/X389-7 TFE BETA
	FABRIC X-389-7 BETA/GLASS/TFE
	INSULATION BLANKET FLUORGLAS 385-3
	LACING TAPE A050
	LACING TAPE PTFE/GLASS
	TAPE 2345-1 KAPTON/SILICONE
	TAPE E125 TEFLON
	TAPE FLUORGLAS 2915 PS ADHESIVE
	TAPE FLUORGLAS ALUMINUM/GLASS SILICONE ADHESIVE
	TAPE FLUORGLAS/TEFLON
	TAPE KAPTON/ACRYLIC ADHESIVE 2342-1R
	TAPE X389-25-1 BETA GL TEFLON
	WIRE ELEC RAYCHEM 44 BETAWRAP
DODGE CORK CO INC	BRAKE MATERIAL F328 CORK COMP
	CORK B-380FA
DODGE WASMUND	SEALANT TEFLON TFE O-RING
	TEFLON TFE VIRGIN
DOLPH CHEMICAL	ADHESIVE DOLPHON CN1119
	PLASTIC DOLFLEX CC1015
	PLASTIC DOLPHON CB1076
	PLASTIC DOLPHON CB1078
	PLASTIC DOLPHON CB1078/RE2000
	PLASTIC DOLPHON CB1078/RE2001
	PLASTIC DOLPHON CB1078/RE2005
	PLASTIC DOLPHON CB1078/RE2009
	PLASTIC DOLPHON CB1078/RE2010
	PLASTIC DOLPHON CB1078/RE2019
	PLASTIC DOLPHON CB1112A/CB1112B
	PLASTIC DOLPHON CB1112A/RE2000
	PLASTIC DOLPHON CB1116
	PLASTIC DOLPHON CC1079/RE2000
DOLPH CHEMICAL	PLASTIC DOLPHON CC1079/RE2005
	PLASTIC DOLPHON CC1095
	PLASTIC DOLPHON CC1106
	PLASTIC DOLPHON CR1035
	PLASTIC DOLPHON CR1050
	VARNISH SYNTHITE AC41 CLF
DOLPH COMPANY	COATING VARNISH HI-THERM BB252 BLACK BAKING
DOLPHIN PAINT & CHEMICAL	ADHESIVE DOLCHEM 3400
	ADHESIVE DOLCHEM 3420
	ADHESIVE DOLCHEM 5072
	ADHESIVE DOLCHEM 6002
	ADHESIVE DOLCHEM 6010
	ADHESIVE DOLCHEM 6016
	ADHESIVE DOLCHEM 6021
	ADHESIVE DOLCHEM 6029
	ADHESIVE DOLCHEM 6034
	ADHESIVE DOLCHEM 6040
	ADHESIVE DOLCHEM 60466
	ADHESIVE DOLCHEM 6060
	ADHESIVE DOLCHEM 6065
	ADHESIVE DOLCHEM 6067
	ADHESIVE DOLCHEM 6068
	ADHESIVE DOLCHEM 6070
	ADHESIVE DOLCHEM 6080
	ADHESIVE DOLCHEM 6100
	ADHESIVE DOLCHEM 6101
	ADHESIVE DOLCHEM 6109
	ADHESIVE DOLCHEM 6110
	ADHESIVE DOLCHEM 6111
	ADHESIVE DOLCHEM 6115
	ADHESIVE DOLCHEM 6116
	ADHESIVE DOLCHEM 6121
	ADHESIVE DOLCHEM 6126
	ADHESIVE DOLCHEM 6203
	ADHESIVE DOLCHEM 6210
	ADHESIVE DOLCHEM 6310/6311
	ADHESIVE DOLCHEM 6420
	ADHESIVE DOLCHEM 6488
	ADHESIVE DOLCHEM 6529
	DOLCHEM 6009
DORCO ELECTRONICS	LAMIN EPOXY/GLASS
	TUBING G10 130C FIBERGLASS/EPOXY
DORNIER	WIRE ELEC ETFE TEFZEL
	WIRE ELEC PTFE/GLASS FEP
	WIRE ELEC TEFLON TFE
DOUGLAS ENGINEERING	CONNECTOR DUCTORSEAL 6837/6838
DOW CHEMICAL	COATING DER 332 RESIN/MXDA CAT
	FILM SARAN 18L
	FILM SARAN 8 CLEAR
	FILM SARAN PSD629/200GA CLEAR
	FOOD RAT/MOUSE
	INSULATION FOAM POLYETHYLENE ETHAFOAM 220
	INSULATION FOAM POLYETHYLENE FLEXIBLE
	INSULATION FOAM STYRENE

MSFC-HDBK-527 REV F 9999942 0006880 7

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
DOW CHEMICAL	INSULATION FOAM STYROFOAM TG BLUE
	INSULATION FOAM UNICELLULAR POLYETHYLENE
	INSULATION POLYSTYRENE/FLUOREL
	INSULATION STYROFOAM TG
	INSULATION STYROFOAM/STYRENE
	PLASTIC CALIBRE 200-10
	PLASTIC CALIBRE 200-15
	PLASTIC CALIBRE 200-22
	PLASTIC CALIBRE 200-4
	PLASTIC CALIBRE 200-6
	PLASTIC CALIBRE 2060-10
	PLASTIC CALIBRE 2060-15
	PLASTIC CALIBRE 2060-22
	PLASTIC CALIBRE 2060-4
	PLASTIC CALIBRE 2060-6
	PLASTIC CALIBRE 2080-15
	PLASTIC CALIBRE 2080-4
	PLASTIC CALIBRE 300-10
	PLASTIC CALIBRE 300-15
	PLASTIC CALIBRE 300-22
	PLASTIC CALIBRE 300-4
	PLASTIC CALIBRE 300-6
	PLASTIC CALIBRE 510
	PLASTIC CALIBRE 550
	PLASTIC CALIBRE 700-10
	PLASTIC CALIBRE 700-15
	PLASTIC CALIBRE 700-6
	PLASTIC CALIBRE 800-10
	PLASTIC CALIBRE 800-15
	PLASTIC CALIBRE 800-6
	PLASTIC DERAKANE 411-45
	PLASTIC DERAKANE 470-36
	PLASTIC DERAKANE 510A-40
	PLASTIC DERAKANE 530
	PLASTIC DERAKANE 8084
	PLASTIC HDPE 25050P
	PLASTIC HDPE 25053P
	PLASTIC HDPE 69065P
	PLASTIC MAGNUM ABS213 RESIN
	PLASTIC MAGNUM ABS341 RESIN
	PLASTIC MAGNUM ABS343 RESIN
	PLASTIC MAGNUM ABS4500UV RESIN
	PLASTIC MAGNUM ABS545 RESIN
	PLASTIC MAGNUM ABS9010 RESIN
	PLASTIC MAGNUM ABS9020 RESIN
	PLASTIC MAGNUM ABS9030 RESIN
	PLASTIC MAGNUM ABS9408 RESIN
	PLASTIC MAGNUM ABS941 RESIN
	PLASTIC MAGNUM ABS9450P RESIN
	PLASTIC MAGNUM ABS95CLR RESIN
	PLASTIC MAGNUM ABSFG960 RESIN
	PLASTIC PULSE ENGINEERING RESINS 600
	PLASTIC PULSE ENGINEERING RESINS 710
	PLASTIC PULSE ENGINEERING RESINS 830
	PLASTIC PULSE ENGINEERING RESINS 855

MANUFACTURER	DESIGNATION
DOW CHEMICAL	PLASTIC PULSE ENGINEERING RESINS 869
	PLASTIC PULSE ENGINEERING RSINS 700
	PLASTIC SAN 125
	PLASTIC SHEET SARNEX #15
	PLASTIC STYRON 656D
	PLASTIC STYRON 666D
	PLASTIC STYRON 678D
	PLASTIC STYRON 678U
	PLASTIC STYRON 685
	PLASTIC STYRON 685D
	PLASTIC STYRON 697
	PLASTIC TYRIL 1000
	PLASTIC TYRIL 1000B
	PLASTIC TYRIL 1020
	PLASTIC TYRIL 1021
	PLASTIC TYRIL 1031
	PLASTIC TYRIL 880
	PLASTIC TYRIL 880B
	RESIN CALIBRE 700-4 POLYCARBONATE COLOR #030003
	RESIN CALIBRE 800-4 POLYCARBONATE .10 INCH SHEET STANDARD BLACK 770001
	RUBBER PELLETHANE 2013-90AEF
	RUBBER PELLETHANE 2102-75A
	RUBBER PELLETHANE 2102-80A
	RUBBER PELLETHANE 2102-80AE
	RUBBER PELLETHANE 2102-80PF
	RUBBER PELLETHANE 2102-85A
	RUBBER PELLETHANE 2102-90A
	RUBBER PELLETHANE 2102-90AE
	RUBBER PELLETHANE 2102-90AR
	RUBBER PELLETHANE 2102-90PF
	RUBBER PELLETHANE 2103-70A
	RUBBER PELLETHANE 2103-80A
	RUBBER PELLETHANE 2103-80AE
	RUBBER PELLETHANE 2103-80AEF
	RUBBER PELLETHANE 2103-80AES
	RUBBER PELLETHANE 2103-80PF
	RUBBER PELLETHANE 2103-80WC
	RUBBER PELLETHANE 2103-85AE
	RUBBER PELLETHANE 2103-90A
	RUBBER PELLETHANE 2103-90ACR
	RUBBER PELLETHANE 2103-90AE
	RUBBER PELLETHANE 2130-85ACR
	RUBBER PELLETHANE 2202-93A
	RUBBER PELLETHANE 2351-85AE
	RUBBER PELLETHANE 2352-70A
	RUBBER PELLETHANE 2355-75A
	RUBBER PELLETHANE 2355-80A
	RUBBER PELLETHANE 2355-80AE
	RUBBER PELLETHANE 2355-80AEF
	RUBBER PELLETHANE 2355-85ABR
	RUBBER PELLETHANE 2355-90A
	RUBBER PELLETHANE 2355-90AE
	RUBBER PELLETHANE 2355-95ACR

MSFC-HDBK-527 REV F 9999942 0006881 9

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
DOW CHEMICAL	RUBBER PELLETHANE 2355-95AE
	RUBBER PELLETHANE 2355-95AEF
	RUBBER PELLETHANE 2355-95AESP
	RUBBER PELLETHANE 2363-75A
	RUBBER PELLETHANE 2363-80A
	RUBBER PELLETHANE 2363-80AE
	RUBBER PELLETHANE 2363-90A
	RUBBER PELLETHANE 2363-90AE
	WIRE ELEC TFE/SARAN WRAPPED
DOW CORNING	ADHESIVE 1890
	ADHESIVE 4-2805
	ADHESIVE 4-2817
	ADHESIVE 738/1204 PRIMER
	ADHESIVE A4000 SILICONE
	ADHESIVE DC 92-009
	ADHESIVE DC281 SILICONE WITH CATALYST
	ADHESIVE DC282
	ADHESIVE DC6-1004
	ADHESIVE DC6-1125
	ADHESIVE DC92-010 RUBBER SILICONE
	ADHESIVE DC92-018 SILICONE
	ADHESIVE DC93-006
	ADHESIVE DC93-118
	ADHESIVE DC94-002 FLUOROSILICONE RUBBER
	ADHESIVE DC94-011
	ADHESIVE DC94-031
	ADHESIVE DC96-069 SILICONE
	ADHESIVE DC96-081 RTV
	ADHESIVE DC96-082 RUBBER SILICONE
	ADHESIVE DC96-083
	ADHESIVE RTV 730/RTV 1200 PRIME COAT
	ADHESIVE RTV 732/RTV 1200 PRIME COAT
	ADHESIVE RTV 738
	ADHESIVE RTV 739
	ADHESIVE RUBBER SILICONE DC280A
	ADHESIVE RUBBER SILICONE RTV 92-076
	ADHESIVE S1017
	ADHESIVE S2288
	ADHESIVE SILICONE DC999
	ADHESIVE SYLGARD 187
	COATING 96-005 SILICONE
	COATING DC 1-2577/C 176
	COATING DC 1107 INSUL FLUID
	COATING DC 1200 SILANE
	COATING DC 1201 CLEAR SILICONE
	COATING DC 1203 SILANE
	COATING DC 1204
	COATING DC 1205
	COATING DC 3140/FLUOREL 7GA
	COATING DC 630 SILICONE
	COATING DC 92-007 SILICONE
	COATING DC 92-046
	COATING DC 93-104 SILICONE
	COATING DC Q3-6500 SILICONE
	COATING DC Z6020 SILANE

MANUFACTURER	DESIGNATION
DOW CORNING	COATING DC Z6031 SILANE
	COATING DC Z6040 SILANE
	COATING DC Z6070 SILANE
	COATING DER 332/VERSAMID 125
	COATING HEXAMETHYLDISILAZNE Z6079
	COATING MOLYKOTE 3400A CORROSION PROTECTIVE
	COATING QR43117X4-176 CAT/SIL
	COATING SILICONE JUNCTION R6101
	COATING SILICONE VESTAR Q9-6503
	COATING SILICONE/PRIMER
	COATING SOLITHANE C113-300/DC3140
	COMPONENT BOARDS DC 1-2577
	FELT NOMEX/DC92-007 SILICONE COATED
	FILM ADHESIVE XT40 110/234
	FILM KYNAR NATURAL TOX RATE STUDY
	GLASS PYREX
	GREASE DC40 SILICONE
	INSULATION AFRSI WITH DISILAZANE Z6079
	INSULATION FOAM PYRELL/RTV 3140 COATING
	INSULATION FOAM SILICONE RTV DC3-6548
	INSULATION FOAM STYROFOAM TG BLUE
	INSULATION STYROFOAM
	INSULATION STYROFOAM WHITE
	LAMIN PRINTED WIRING BOARD /DC3140 COATED
	LUBE DRY MOLYKOTE 3
	LUBE DRY MOLYKOTE 321R
	LUBE DRY MOLYKOTE 33
	LUBE DRY MOLYKOTE 33 TOX RATE STUDY
	LUBE DRY MOLYKOTE 44
	LUBE DRY MOLYKOTE 505
	LUBE DRY MOLYKOTE 55M
	LUBE DRY MOLYKOTE G
	LUBE DRY MOLYKOTE G-N
	LUBE DRY MOLYKOTE L
	LUBE DRY MOLYKOTE Z MOS2 INORGANIC
	LUBE DRY SPRAYKOTE MOS2/SILICONE
	LUBE GREASE DC11 SILICONE
	LUBE GREASE DC111 SILICONE
	LUBE GREASE DC112 SILICONE
	LUBE GREASE DC2 SILICONE
	LUBE GREASE DC4 SILICONE
	LUBE GREASE DC970V SILICONE
	LUBE GREASE HIGH VACUUM SILICONE
	LUBE GREASE SILICONE
	LUBE GREASE SILICONE DC5
	LUBE GREASE SILICONE DC971V
	LUBE GREASE STOPCOCK SILICONE
	LUBE GREASE THERMAL DC340 HS
	LUBE GREASE X5-8003 SILICONE
	LUBE OIL DC200 SILICONE
	LUBE OIL DC510 SILICONE
	LUBE OIL SILICONE F6-1101
	MOLD COMPOUND DC302 SILICONE
	PLASTIC 1-5021

MSFC-HDBK-527 REV F 9999942 0006882 0

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
DOW CORNING	PLASTIC 307
	PLASTIC 308
	PLASTIC 480
	PLASTIC 631
	PLASTIC Q1-5036
	POTTING COMPOUND 93-500/ALUMINUM-OXIDE FILL
	POTTING COMPOUND 93-500/CU MICROSPHER
	POTTING COMPOUND DC183
	POTTING COMPOUND DC4040 FLUOROSILICONE
	POTTING COMPOUND DC7521 SILICONE
	POTTING COMPOUND ECN1235/ALUMINUM-OXIDE F
	POTTING COMPOUND POLYURETHANE DC902-1
	POTTING COMPOUND SCOTCHCAST 8/DC3140
	POTTING COMPOUND SYLGARD 170
	POTTING COMPOUND SYLGARD 182
	POTTING COMPOUND SYLGARD 183
	POTTING COMPOUND SYLGARD 184
	POTTING COMPOUND SYLGARD 186
	RUBBER 3-6550
	RUBBER FLUOROSILICONE LS2323
	RUBBER FLUOROSILICONE LS53
	RUBBER FLUOROSILICONE LS63
	RUBBER FLUOROSILICONE RTV 733
	RUBBER S5370
	RUBBER SILASTIC 1890
	RUBBER SILASTIC 35U
	RUBBER SILASTIC 437 BASE
	RUBBER SILASTIC 55U SILICONE
	RUBBER SILASTIC 55U/75U
	RUBBER SILASTIC 590
	RUBBER SILASTIC 591
	RUBBER SILASTIC 595
	RUBBER SILASTIC 596
	RUBBER SILASTIC 598
	RUBBER SILASTIC 599
	RUBBER SILASTIC 735
	RUBBER SILASTIC 745U
	RUBBER SILASTIC 746U
	RUBBER SILASTIC 747
	RUBBER SILASTIC 747U
	RUBBER SILASTIC 75U
	RUBBER SILASTIC 75U/8PPH CAB-O-SIL MS7/DMBPH
	RUBBER SILASTIC DC55
	RUBBER SILASTIC DC675
	RUBBER SILASTIC FORMULA A
	RUBBER SILASTIC FORMULA B
	RUBBER SILASTIC FORMULA C
	RUBBER SILASTIC FORMULA D
	RUBBER SILASTIC GP437
	RUBBER SILASTIC GP45
	RUBBER SILASTIC GP70
	RUBBER SILASTIC HS
	RUBBER SILASTIC HS30

MANUFACTURER	DESIGNATION
DOW CORNING	RUBBER SILASTIC HS30/HS50
	RUBBER SILASTIC HS50
	RUBBER SILASTIC HS50/HS70
	RUBBER SILASTIC HS70
	RUBBER SILASTIC J
	RUBBER SILASTIC L
	RUBBER SILASTIC LCS740
	RUBBER SILASTIC LS2249U
	RUBBER SILASTIC LS2311U
	RUBBER SILASTIC LS2380U
	RUBBER SILASTIC LS2840
	RUBBER SILASTIC LS2860
	RUBBER SILASTIC LS53U
	RUBBER SILASTIC LS63U
	RUBBER SILASTIC LT40/RED
	RUBBER SILASTIC LT40/WHITE
	RUBBER SILASTIC LT50
	RUBBER SILASTIC NPC40
	RUBBER SILASTIC NPC40/NPC80
	RUBBER SILASTIC NPC80
	RUBBER SILASTIC RTV 731
	RUBBER SILASTIC RTV 732
	RUBBER SILICONE 'E'
	RUBBER SILICONE 24037 CARBON/FILLED
	RUBBER SILICONE 382 MEDICAL SI
	RUBBER SILICONE 434
	RUBBER SILICONE DC CF217U
	RUBBER SILICONE DC Q3-6567 A/B
	RUBBER SILICONE DC8-2318U
	RUBBER SILICONE DC90-006
	RUBBER SILICONE DC93-072
	RUBBER SILICONE DC93-076
	RUBBER SILICONE DC93-500
	RUBBER SILICONE MDX4-4210 MEDICAL GRADE
	RUBBER SILICONE MEDICAL GRADE
	RUBBER SILICONE ON AL/SILASTIC E
	RUBBER SILICONE R425
	RUBBER SILICONE RTV 140
	RUBBER SILICONE RTV 2318
	RUBBER SILICONE RTV 282 ADHESIVE
	RUBBER SILICONE RTV 30-121
	RUBBER SILICONE RTV 3110
	RUBBER SILICONE RTV 3112
	RUBBER SILICONE RTV 3112/CATALYST F
	RUBBER SILICONE RTV 3116
	RUBBER SILICONE RTV 3118
	RUBBER SILICONE RTV 3120
	RUBBER SILICONE RTV 3140
	RUBBER SILICONE RTV 3140 TOX RATE STUDY
	RUBBER SILICONE RTV 3140 UNCURED
	RUBBER SILICONE RTV 3140/1204
	RUBBER SILICONE RTV 3144
	RUBBER SILICONE RTV 3145
	RUBBER SILICONE RTV 3145/DC1200
	RUBBER SILICONE RTV 325

MSFC-HDBK-527 REV F 9999942 0006883 2

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
DOW CORNING	RUBBER SILICONE RTV 345
	RUBBER SILICONE RTV 4515
	RUBBER SILICONE RTV 501-7
	RUBBER SILICONE RTV 6508
	RUBBER SILICONE RTV 651
	RUBBER SILICONE RTV 69-210
	RUBBER SILICONE RTV 730
	RUBBER SILICONE RTV 738
	RUBBER SILICONE RTV 955
	RUBBER SILICONE RTV DC3-6077
	RUBBER SILICONE RTV DC6-1104
	RUBBER SILICONE RTV DC96-080
	RUBBER SILICONE S6535
	RUBBER SILICONE SM3500-41
	RUBBER SYLGARD 527
	RUBBER SYLGARD 567
	RUBBER SYLGARD 577
	RUBBER URINE COLLECTION TUBE
	TUBING NICALON
	TUBING SILASTIC P/N 601405
	TUBING SILASTIC P/N VWR62999-405
	TUBING SILICONE P/N 1665618
	TUBING SILICONE RX50 SILASTIC
	VARNISH SILICONE DC997
DOW CORNING/SHELL CHEMICAL/FURANE	COATING RTV DC Q36077 ABLATIVE/EPON 828/ EPOCAST 951
DR. DANIEL WOODARD	ADHESIVE DAC1
DRAGON VALVES INC	KEL-F CTFE UNPLASTICIZED
	RUBBER VITON V747-75
DREW CHEMICAL CORP	DREWGARD 100
	DREWGARD 187
DRILUBE CO	LUBE DRY 701 OXYLUBE INORGANIC
	LUBE DRY DRILUBE 1A
	LUBE DRY DRILUBE 6A
	LUBE DRY DRILUBE 822
	LUBE DRY DRILUBE 842
	LUBE DRY INVELCO 33F
DRITZ	BRAID ELASTIC NYLON/RUBBER
	BRAID ELASTIC POLYESTER
	BRAID NYLON ELASTIC
DRUMMOND	MICROHEMATOCRIT TUBE HOLDER
DRYCORE FELT CO	FABRIC NOMEX 2PLY/FELT-1PLY
	FELT NOMEX
DUBOIS CHEMICALS	ADHESIVE DUHESIVE SPRAY
	LUBE GREASE POLYMER MPG2
DUCO	ADHESIVE DUCO
DUPONT	ADHESIVE 5504 EPOXY/AG
	ADHESIVE ADIPRENE L100/ALUMINUM OXIDE
	ADHESIVE AVIMID N COMPOSITE
	ADHESIVE CAVALON 3300S/3101S
	ADHESIVE FAIRPRENE V2-5159
	ADHESIVE FILM LF0400 PYRALUX
	ADHESIVE HYLENE M50
	ADHESIVE PYRALUX WA/A
	ADHESIVE TERATHANE POLYETHER GLOCOLS

MANUFACTURER	DESIGNATION
DUPONT	ADHESIVE VOLAN 9720PP
	ADHESIVE ZIRCORE FOUNDRY SAND
	ARMALON
	ARMALON IMPREGNATED WITH KRYTOX 143 AZ
	ARMALON TG 4102
	ARMALON TG 4140
	ARMALON XT 7XXXX
	COATING 02-GY-3 WITH KEVLAR LAMIN
	COATING 401-B2 GRAY
	COATING 5205U PAINT WITH 8248 PRIMER
	COATING 6543U/PRIMER 8245
	COATING 6561U PAINT WITH EPOXY PRIMER
	COATING 7414/PRIMER EPOXY 8245
	COATING 850-204 TFE GREEN
	COATING 850-204/851-214 GREEN
	COATING 850-204/851-225/856-204
	COATING 850-204/851-245/856-204
	COATING 850-204/855-225 TFE
	COATING 851-204 TEFLON PRIMER
	COATING 851-204/851-224 TFE
	COATING 851-224 GREEN/850-204 GREEN
	COATING 851-225 BLK/850-201
	COATING 851-245 TOPCOAT/850-204 PRIMER
	COATING 856-204 TFE GREEN/851-255 TFE
	BLACK/850-204 TFE GREEN PRIMER
	COATING 856-204/855-225/850-204
	COATING 958-203 TEFLON
	COATING 959-203 TFE BLACK
	COATING AR7 WITH KRYTOX 240AC
	COATING PREPARAKOAT 3055S
	COATING PTFE DISPERSION
	COATING PYRE ML
	COATING RK692
	COATING RK692 PYRE ML
	COATING S954-207 TEFLON
	COATING TFE 1 COAT GRAY
	COMPOSITE VITON E60C/NOMEX HT426
	CONFIGURATION NOMEX/RTV
	CORD KEVLAR
	CORD KEVLAR 1600 KDE 29 ARAMID
	CORD KEVLAR B275
	DELRIN 500
	DELRIN ACETAL
	FABRIC BETA/TFE COATED 95-049
	FABRIC FAIRPRENE VT007 TFE/VITON
	FABRIC HT-337 NOMEX
	FABRIC HT-6-42/NOMEX
	FABRIC KEVLAR 102-123-2 COATED VITON
	FABRIC NOMEX 200 DENIER
	FABRIC NOMEX 7878 G650
	FABRIC NOMEX ARAMID FR P/N E-2
	FABRIC NOMEX ARAMID NAVY BLUE
	FABRIC NOMEX WITH ZEPEL/ARMALON
	FABRIC NOMEX WITH ZEPEL/ARMALON/URETHANE
	COATED NY

MSFC-HDBK-527 REV F 9999942 0006884 4

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
DUPONT	FABRIC NOMEX/ARMALON BACKING
	FABRIC NOMEX/ARMALON/URETHANE COATED NY
	FABRIC TACONIC 7159-128 TEFLON
	FABRIC TEFLON 30
	FABRIC TYVEK 1442
	FABRIC VD0001 DACRON/VITON
	FELT NOMEX STYLE 22NX
	FELT TFE
	FILM CRONALAR HIGH ACUTANCE HA4 CRONAR CLEAR POLYESTER HIGH CONTRAST NEGATIVE WORKING FILM
	FILM CRONALAR HIGH ACUTANCE HA7 CRONAR CLEAR POLYESTER HIGH CONTRAST NEGATIVE WORKING FILM
	FILM CRONAPAQUE CPF7 WHITE SEMI-OPAQUE
	FILM ELVANOL 71-30 PVA
	FILM KAPTON F150F019
	FILM KAPTON H
	FILM KAPTON HF POLYIMIDE
	FILM KAPTON/FEP TEFLON
	FILM LMC300 KAPTON
	FILM MYLAR "S"
	FILM MYLAR 105 CLEAR/JCP E20
	FILM MYLAR 205 RED/JCP E20
	FILM MYLAR 305 YELLOW/JCP E20
	FILM MYLAR 315 LTYEEL/JCP E20
	FILM MYLAR 505 ORANGE/JCP E20
	FILM MYLAR 615 LT GRN/JCP E20
	FILM MYLAR 805 PURPLE/JCP E20
	FILM MYLAR 915 BROWN/JCP E20
	FILM MYLAR POLYESTER
	FILM MYLAR TYPE A
	FILM PHOTO EN7
	FILM PHOTOGRAPHIC EN4
	FILM RISTON 730FR
	FILM SAN
	FILM TEDLAR 200BG30 PVF
	FILM TEDLAR 400 BS 30 WHITE
	FILM TEDLAR POLYVINYL FLUORIDE
	FILM TEDLAR PVF 150 BLACK 30CC
	FILM TEFLON FEP
	GASKET GYLON 1/16"
	INSULATION FOAM NEOPRENE NOC
	INSULATION NOMEX 410/KAP/LDR PAPER
	INSULATION PYRALUX POLYIMIDE
	KEL-F 800 MEK/SPRAY
	LACING TAPE NOMEX 431 SBR/ML
	LAMIN EPOXY/GLASS DX501/7581/181
	LAMIN EPOXY/KEVLAR DSX501/181 KEVLAR 49
	LAMIN FIBERFRAX T30LR (INORGANIC)
	LAMIN POLYIMIDE/GLASS
	LUBE DRY 958-301 TEFLON
	LUBE GREASE KRYTOX 21
	LUBE GREASE KRYTOX 240AB
	LUBE GREASE KRYTOX 240AC

MANUFACTURER	DESIGNATION
DUPONT	LUBE GREASE KRYTOX 240AD
	LUBE GREASE KRYTOX 240AZ
	LUBE GREASE KRYTOX 250AB
	LUBE GREASE KRYTOX 283AB
	LUBE GREASE KRYTOX GPL103
	LUBE OIL KRYTOX 143AC
	MOLD COMPOUND POLYPHENYLENE OXIDE
	MULTI-LAYERED INSULATION ALUMINIZED KAPTON/ALUMINIZED MYLAR/DACRON/NOMEX
	MULTI-LAYERED INSULATION TEDLAR/ALUMINIZED MYLAR
	MULTI-LAYERED INSULATION TEDLAR/MYLAR/ VELCRO #65
	NYLON 12
	NYLON 6/6 ZYTEL 101
	NYLON/15% GLASS
	PAPER 414 NOMEX
	PAPER FIBERFRAX
	PAPER NOMEX TYPE 410/ARAMID
	PAPER TYVEK
	PAPER TYVEK STYLE 1073D
	PLASTIC ALATHON 20
	PLASTIC ALATHON 20-6064
	PLASTIC ALATHON 2005
	PLASTIC ALATHON 2010
	PLASTIC ALATHON 2020
	PLASTIC ALATHON 2020T
	PLASTIC BN101 ACRYLIC PVC
	PLASTIC CHLORINATED POLYETHER
	PLASTIC DELRIN 100
	PLASTIC DELRIN 100AF
	PLASTIC DELRIN 100CL
	PLASTIC DELRIN 100D
	PLASTIC DELRIN 100F
	PLASTIC DELRIN 100ST
	PLASTIC DELRIN 107
	PLASTIC DELRIN 150SA
	PLASTIC DELRIN 200PL
	PLASTIC DELRIN 500AF
	PLASTIC DELRIN 500CL
	PLASTIC DELRIN 500D
	PLASTIC DELRIN 500F
	PLASTIC DELRIN 500HP
	PLASTIC DELRIN 500T
	PLASTIC DELRIN 507
	PLASTIC DELRIN 510AF
	PLASTIC DELRIN 550SA
	PLASTIC DELRIN 570
	PLASTIC DELRIN 577
	PLASTIC DELRIN 900
	PLASTIC DELRIN 900D
	PLASTIC DELRIN 900F
	PLASTIC DELRIN 900HP
	PLASTIC DELRIN 907F
	PLASTIC DKE450/ACRYLIC PVC

MSFC-HDBK-527 REV F 9999942 0006885 6

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
DUPONT	PLASTIC ELVAMIDE 8023
	PLASTIC ELVAMIDE 8061
	PLASTIC ELVAMIDE 8061M
	PLASTIC ELVAMIDE 8062S
	PLASTIC ELVAMIDE 8063
	PLASTIC ELVAMIDE 8064
	PLASTIC ELVAMIDE 8066
	PLASTIC ELVAX 150
	PLASTIC ELVAX 240
	PLASTIC ELVAX 250
	PLASTIC ELVAX 260
	PLASTIC ELVAX 265
	PLASTIC ELVAX 350
	PLASTIC ELVAX 360
	PLASTIC ELVAX 40W
	PLASTIC ELVAX 450
	PLASTIC ELVAX 46
	PLASTIC ELVAX 460
	PLASTIC ELVAX 46L
	PLASTIC ELVAX 470
	PLASTIC ELVAX 550
	PLASTIC ELVAX 560
	PLASTIC ELVAX 565
	PLASTIC ELVAX 650
	PLASTIC ELVAX 660
	PLASTIC ELVAX 670
	PLASTIC ELVAX 750
	PLASTIC ELVAX 760
	PLASTIC ELVAX 770
	PLASTIC ELVAX LDPE
	PLASTIC GRZ 70G13 HS1L
	PLASTIC GRZ 70G13L
	PLASTIC GRZ 70G33 HRL
	PLASTIC GRZ 70G33 HS1L
	PLASTIC GRZ 70G33 HS1L 70G43L
	PLASTIC GRZ 70G33L
	PLASTIC GRZ 70G43L
	PLASTIC GRZ 71G13L
	PLASTIC GRZ 71G33L
	PLASTIC GRZ 77G33L
	PLASTIC GRZ 77G43L
	PLASTIC GRZ 80G33HS1L
	PLASTIC KAPTON POLYIMIDE FILM
	PLASTIC KAPTON TYPE H
	PLASTIC KELDAX 6826Q
	PLASTIC KELDAX 8208
	PLASTIC KELDAX 8208Q
	PLASTIC KELDAX 9103
	PLASTIC KELDAX 9105
	PLASTIC KELDAX 9106
	PLASTIC MINLON 10B
	PLASTIC MINLON 11C
	PLASTIC MINLON 12T
	PLASTIC MINLON 20B
	PLASTIC MINLON 21C

MANUFACTURER	DESIGNATION
DUPONT	PLASTIC MINLON 22C
	PLASTIC MINLON 91C
	PLASTIC MINLON FR60
	PLASTIC MYLAR
	PLASTIC NUCREL 010
	PLASTIC NUCREL 035
	PLASTIC NUCREL 403
	PLASTIC NUCREL 410
	PLASTIC NUCREL 535
	PLASTIC NUCREL 599
	PLASTIC NUCREL 699
	PLASTIC NUCREL 714
	PLASTIC NUCREL 925
	PLASTIC NUCREL 960
	PLASTIC RYNITE 430
	PLASTIC RYNITE 530
	PLASTIC RYNITE 545
	PLASTIC RYNITE 555
	PLASTIC RYNITE 935
	PLASTIC RYNITE 940
	PLASTIC RYNITE 940FB
	PLASTIC RYNITE FR543
	PLASTIC RYNITE FR945
	PLASTIC RYNITE RF530
	PLASTIC RYNITE SST35
	PLASTIC SURLYN 8020
	PLASTIC SURLYN 8528
	PLASTIC SURLYN 8550
	PLASTIC SURLYN 8660
	PLASTIC SURLYN 8920
	PLASTIC SURLYN 8940
	PLASTIC SURLYN 9020
	PLASTIC SURLYN 9450
	PLASTIC SURLYN 9520
	PLASTIC SURLYN 9650
	PLASTIC SURLYN 9721
	PLASTIC SURLYN 9730
	PLASTIC SURLYN 9910
	PLASTIC SURLYN 9950
	PLASTIC SURLYN 9970
	PLASTIC TEDLAR
	PLASTIC TEFLON 62 TFE
	PLASTIC TEFLON 67 TFE
	PLASTIC TEFLON 6C PTFE
	PLASTIC TEFLON FEP 100
	PLASTIC TEFLON FEP 120
	PLASTIC TEFLON FEP 140
	PLASTIC TEFLON TFE 160
	PLASTIC TEFLON TFE 60
	PLASTIC TEFLON TFE 64
	PLASTIC TEFLON TFE 65
	PLASTIC TEFLON TFE 66
	PLASTIC TEFLON TFE 8
	PLASTIC TEFLON TFE 8A
	PLASTIC TEFLON TFE 8B

MSFC-HDBK-527 REV F 9999942 0006886 8

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
DUPONT	PLASTIC TEFLON TFE 9B
	PLASTIC ZYTEL 101
	PLASTIC ZYTEL 101L
	PLASTIC ZYTEL 105
	PLASTIC ZYTEL 109L
	PLASTIC ZYTEL 133C
	PLASTIC ZYTEL 158C
	PLASTIC ZYTEL 211
	PLASTIC ZYTEL 408
	PLASTIC ZYTEL 408 HS
	PLASTIC ZYTEL 408C
	PLASTIC ZYTEL 42
	PLASTIC ZYTEL 91 HS
	PLASTIC ZYTEL ST 801
	PLASTIC ZYTEL ST 811
	PLASTIC ZYTEL ST 811 HS
	RUBBER CHLOROPRENE VONAR 3
	RUBBER FAIRPRENE 5159
	RUBBER FAIRPRENE DS0001
	RUBBER FAIRPRENE SR554D
	RUBBER KALREZ 1004
	RUBBER KALREZ 1018
	RUBBER KALREZ 1045
	RUBBER KALREZ 1045R
	RUBBER KALREZ 1046R
	RUBBER KALREZ 1046R2
	RUBBER KALREZ 1046R2M
	RUBBER KALREZ 1046RM
	RUBBER KALREZ 1050
	RUBBER KALREZ 1058
	RUBBER KALREZ 3018
	RUBBER KALREZ 3065
	RUBBER KALREZ 4079 COMPOUND
	RUBBER NEOPRENE NS6022
	RUBBER NORDEL EPT75
	RUBBER SILICONE HARDNESS SHORE "A" 45-55
	RUBBER VITON E43060
	RUBBER VITON E46315
	RUBBER VITON E60C
	RUBBER VITON E60C/HT426 NOMEX
	RUBBER VITON GF CPD SEE REPORT
	RUBBER VITON VD000B
	SPONGE RUBBER NEOPRENE
	TAPE KAPTON AND TAPE HOLDER
	TAPE POLYESTER 415/ACRYLIC ADHESIVE
	TEFLON FEP
	TEFLON TFE VIRGIN
	TEFLON TFE/1% CARBON BLACK
	TEFLON TFE/15% GLASS
	TEFZEL ETFE
	VESPEL KS105
	VESPEL SP-22
	VESPEL SP1/POLYIMIDE
	VESPEL SP21
	VESPEL SP211 POLYIMIDE/GRAPHITE/TFE
DUPONT	VESPEL SP3
	VESPEL SP5 POLYIMIDE/GLASS
	VYDAX 1000
	VYDAX AR FLUOROCARBON
	WEBBING NYLON/VELCRO/NOMEX/METALIZED
	UTILITY STRAP
	YARN 200-100-R79-430 NOMEX
	YARN KELVAR 29 TYPE 964
	YARN NOMEX R79-430
	YARN TFE TYPE 302
DURACELL U S A	BATTERY DRY BA1568/U 14 VOLTS
	BATTERY DURACELL 9 VOLT MN1604
	BATTERY DURACELL HG RM12R 1.35
	BATTERY DURACELL HG SIZE AA/ZM9
	BATTERY DURACELL SIZE AA MN1500
	BATTERY MALLORY PX288
DURACOTE CORPORATION	DURA-TUFF #4776
DURAGRAPH SYSTEMS	INK DURAGRAPH B20082 AL RED
DURAMIC PRODUCTS	CERAMIC MACOR (INORGANIC)
DURAY INC	SOAP DISH TRAVEL
DYKEM CORP	STAIN TRANSPARENT
DYMO INC	TAPE SCOTCH 5201-8 EMBOSSING
DYNA SYSTEMS	TUBING POLYOLEFIN HST THERMAPOD
DYNACHEM	INK DYNACURE LETTERING
DYNAMOLD INC	PLASTIC DYNAMOLD DMS4-828
	PLASTIC DYNAMOLD MS26
DYNASIL CORP	SILICA DYNASIL 5000 FUSED INORGANIC
DYNATHERM CORP	COATING D4375 VITON
E B INDUSTRIES	ADHESIVE CUPRINOL OUTDOOR CAULK
	ADHESIVE POLYSEAMSEAL 2002 CLEAR CAULK
	ADHESIVE POLYSEAMSEAL ALL PURPOSE CAULK
E F HOUGHTON & CO	LUBE OIL HOUGHTO-SAFE 1055
	LUBE OIL HOUGHTO-SAFE 1120
	RUBBER NITRILE 1070W VIX
E N MURRAY COMPANY	ABSORBER AFONIC VIBRASORB
	ADHESIVE ADCAM 760
	INSULATION FOAM PYRELL AFONIC ACCOUSTICAL POLYURETHANE
E P S LOGISTICS TECH	PLASTIC DRICLAD PVC NORMAL GRADE GRAY COLOR
E R CARPENTER	INSULATION FOAM URETHANE FR G73C
	INSULATION FOAM URETHANE FR Q31
E/M LUBRICANTS	LUBE DRY ESNA 382
	LUBE DRY EVERLUBE 811
	LUBE DRY EVERLUBE 812
	LUBE DRY INLOX 88
	LUBE DRY MICROSEAL 100-1
	LUBE DRY MICROSEAL 200-1 INORGANIC
	LUBE EVERLUBE 620 SEE TEST RPT
EAGLE-PICHER IND	PLASTIC EP5182
	PLASTIC EP5282
	PLASTIC EPBGC184
	PLASTIC EPBGC78-3
	PLASTIC EPBLE70-12
	PLASTIC EPSG154

MSFC-HDBK-527 REV F 9999942 0006887 T

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
EAGLE-PICHER IND	PLASTIC EPSL142
	PLASTIC EPSL166
	PLASTIC EPSL174
	PLASTIC EPSL186
	PLASTIC EPSL199
	PLASTIC EPSL201
	PLASTIC EPSL202
	PLASTIC EPSL203
	PLASTIC EPSL208
	PLASTIC EPSL213
	PLASTIC EPSL218-1
	PLASTIC EPSLE114-1
	PLASTIC EPSLE174
	PLASTIC EPSLE211
EAR CORP	ABSORBER ENERGY EAR 1002
	ABSORBER ENERGY EAR C2003/ADH
EASTERN MTN SPORTS	SLIPPER SOCKS
EASTMAN CHEMICAL PRODUCTS INC	PLASTIC FOAMABLE TENITE POLYPROPYLENE
	P2635-08AA
	PLASTIC KODAR COPOLYSTER A150 ADHESIVE
	PLASTIC KODAR PETG COPOLYSTER 6763
	PLASTIC PROPIONATE FORMULA 350 H3
	PLASTIC TENITE ACETATE FORMULA 007 H
	PLASTIC TENITE ACETATE FORMULA 007 H2
	PLASTIC TENITE ACETATE FORMULA 007 H3
	PLASTIC TENITE ACETATE FORMULA 007 H4
	PLASTIC TENITE ACETATE FORMULA 007 M
	PLASTIC TENITE ACETATE FORMULA 007 MH
	PLASTIC TENITE ACETATE FORMULA 007 MS
	PLASTIC TENITE ACETATE FORMULA 007 S
	PLASTIC TENITE ACETATE FORMULA 036 H
	PLASTIC TENITE ACETATE FORMULA 036 H2
	PLASTIC TENITE ACETATE FORMULA 036 H3
	PLASTIC TENITE ACETATE FORMULA 036 H4
	PLASTIC TENITE ACETATE FORMULA 036 M
	PLASTIC TENITE ACETATE FORMULA 036 M4
	PLASTIC TENITE ACETATE FORMULA 036 MS
	PLASTIC TENITE ACETATE FORMULA 042 H
	PLASTIC TENITE ACETATE FORMULA 042 H2
	PLASTIC TENITE ACETATE FORMULA 042 H3
	PLASTIC TENITE ACETATE FORMULA 042 H4
	PLASTIC TENITE ACETATE FORMULA 042 M
	PLASTIC TENITE ACETATE FORMULA 042 MH
	PLASTIC TENITE ACETATE FORMULA 042 MS
	PLASTIC TENITE ACETATE FORMULA 042 S2
	PLASTIC TENITE ACETATE FORMULA 043 H
	PLASTIC TENITE ACETATE FORMULA 043 H2
	PLASTIC TENITE ACETATE FORMULA 043 H3
	PLASTIC TENITE ACETATE FORMULA 043 H4
	PLASTIC TENITE ACETATE FORMULA 043 M
	PLASTIC TENITE ACETATE FORMULA 043 MH
	PLASTIC TENITE ACETATE FORMULA 043 MS
	PLASTIC TENITE ACETATE FORMULA 043 S
	PLASTIC TENITE ACETATE FORMULA 043 S2
	PLASTIC TENITE ACETATE FORMULA 054 H

MANUFACTURER	DESIGNATION
EASTMAN CHEMICAL PRODUCTS INC	PLASTIC TENITE ACETATE FORMULA 054 H2
	PLASTIC TENITE ACETATE FORMULA 054 H3
	PLASTIC TENITE ACETATE FORMULA 054 H4
	PLASTIC TENITE ACETATE FORMULA 054 M
	PLASTIC TENITE ACETATE FORMULA 054 M4
	PLASTIC TENITE ACETATE FORMULA 054 MS
	PLASTIC TENITE ACETATE FORMULA 054 S
	PLASTIC TENITE ACETATE FORMULA 100 H
	PLASTIC TENITE ACETATE FORMULA 100 H2
	PLASTIC TENITE ACETATE FORMULA 100 H3
	PLASTIC TENITE ACETATE FORMULA 100 H4
	PLASTIC TENITE ACETATE FORMULA 100 M
	PLASTIC TENITE ACETATE FORMULA 100 MH
	PLASTIC TENITE ACETATE FORMULA 100 MS
	PLASTIC TENITE ACETATE FORMULA 103 H
	PLASTIC TENITE ACETATE FORMULA 103 H2
	PLASTIC TENITE ACETATE FORMULA 103 H3
	PLASTIC TENITE ACETATE FORMULA 103 H4
	PLASTIC TENITE ACETATE FORMULA 103 M
	PLASTIC TENITE ACETATE FORMULA 103 MH
	PLASTIC TENITE ACETATE FORMULA 103 MS
	PLASTIC TENITE ACETATE FORMULA 104 H
	PLASTIC TENITE ACETATE FORMULA 104 H2
	PLASTIC TENITE ACETATE FORMULA 104 H3
	PLASTIC TENITE BUTYRATE FORMULA 203 H
	PLASTIC TENITE BUTYRATE FORMULA 203 H2
	PLASTIC TENITE BUTYRATE FORMULA 203 H3
	PLASTIC TENITE BUTYRATE FORMULA 203 H4
	PLASTIC TENITE BUTYRATE FORMULA 203 M
	PLASTIC TENITE BUTYRATE FORMULA 203 MH
	PLASTIC TENITE BUTYRATE FORMULA 203 MS
	PLASTIC TENITE BUTYRATE FORMULA 203 S
	PLASTIC TENITE BUTYRATE FORMULA 203 S2
	PLASTIC TENITE BUTYRATE FORMULA 205 H
	PLASTIC TENITE BUTYRATE FORMULA 205 H2
	PLASTIC TENITE BUTYRATE FORMULA 205 H3
	PLASTIC TENITE BUTYRATE FORMULA 205 H4
	PLASTIC TENITE BUTYRATE FORMULA 205 M
	PLASTIC TENITE BUTYRATE FORMULA 205 M4
	PLASTIC TENITE BUTYRATE FORMULA 205 MS
	PLASTIC TENITE BUTYRATE FORMULA 205 S
	PLASTIC TENITE BUTYRATE FORMULA 205 S2
	PLASTIC TENITE BUTYRATE FORMULA 217 H
	PLASTIC TENITE BUTYRATE FORMULA 217 H2
	PLASTIC TENITE BUTYRATE FORMULA 217 H3
	PLASTIC TENITE BUTYRATE FORMULA 217 H4
	PLASTIC TENITE BUTYRATE FORMULA 217 M
	PLASTIC TENITE BUTYRATE FORMULA 217 MH
	PLASTIC TENITE BUTYRATE FORMULA 217 MS
	PLASTIC TENITE BUTYRATE FORMULA 217 S
	PLASTIC TENITE BUTYRATE FORMULA 217 S2
	PLASTIC TENITE BUTYRATE FORMULA 236 H
	PLASTIC TENITE BUTYRATE FORMULA 236 H2
	PLASTIC TENITE BUTYRATE FORMULA 236 H3
	PLASTIC TENITE BUTYRATE FORMULA 236 H4

MSFC-HDBK-527 REV F 9999942 0006888 1

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
EASTMAN CHEMICAL PRODUCTS INC	PLASTIC TENITE BUTYRATE FORMULA 236 MH
	PLASTIC TENITE BUTYRATE FORMULA 236 MS
	PLASTIC TENITE BUTYRATE FORMULA 236 S
	PLASTIC TENITE BUTYRATE FORMULA 236-M
	PLASTIC TENITE BUTYRATE FORMULA 264 H
	PLASTIC TENITE BUTYRATE FORMULA 264 H2
	PLASTIC TENITE BUTYRATE FORMULA 264 H3
	PLASTIC TENITE BUTYRATE FORMULA 264 H4
	PLASTIC TENITE BUTYRATE FORMULA 264 M
	PLASTIC TENITE BUTYRATE FORMULA 264 M4
	PLASTIC TENITE BUTYRATE FORMULA 264 MS
	PLASTIC TENITE BUTYRATE FORMULA 264 S
	PLASTIC TENITE BUTYRATE FORMULA 264 S2
	PLASTIC TENITE BUTYRATE FORMULA 479 H
	PLASTIC TENITE BUTYRATE FORMULA 479 H2
	PLASTIC TENITE BUTYRATE FORMULA 479 H3
	PLASTIC TENITE BUTYRATE FORMULA 479 H4
	PLASTIC TENITE BUTYRATE FORMULA 479 M
	PLASTIC TENITE BUTYRATE FORMULA 479 MH
	PLASTIC TENITE BUTYRATE FORMULA 479 MS
	PLASTIC TENITE BUTYRATE FORMULA 525 H
	PLASTIC TENITE BUTYRATE FORMULA 525 H2
	PLASTIC TENITE BUTYRATE FORMULA 525 H3
	PLASTIC TENITE BUTYRATE FORMULA 525 H4
	PLASTIC TENITE BUTYRATE FORMULA 525 M
	PLASTIC TENITE BUTYRATE FORMULA 525 M4
	PLASTIC TENITE BUTYRATE FORMULA 525 MS
	PLASTIC TENITE BUTYRATE FORMULA 525 S
	PLASTIC TENITE BUTYRATE FORMULA 525 S2
	PLASTIC TENITE BUTYRATE FORMULA 554 H
	PLASTIC TENITE BUTYRATE FORMULA 554 H2
	PLASTIC TENITE BUTYRATE FORMULA 554 H3
	PLASTIC TENITE BUTYRATE FORMULA 554 H4
	PLASTIC TENITE BUTYRATE FORMULA 554 M
	PLASTIC TENITE BUTYRATE FORMULA 554 MH
	PLASTIC TENITE BUTYRATE FORMULA 554 MS
	PLASTIC TENITE BUTYRATE FORMULA 554 S
	PLASTIC TENITE BUTYRATE FORMULA 554 S2
	PLASTIC TENITE POLYALLOMER 5020
	PLASTIC TENITE POLYALLOMER 5021
	PLASTIC TENITE POLYALLOMER 512V
	PLASTIC TENITE POLYALLOMER 5151
	PLASTIC TENITE POLYETHYLENE 1390P
	PLASTIC TENITE POLYETHYLENE 1540F
	PLASTIC TENITE POLYETHYLENE 1550
	PLASTIC TENITE POLYETHYLENE 155W
	PLASTIC TENITE POLYETHYLENE 1800
	PLASTIC TENITE POLYETHYLENE 1810
	PLASTIC TENITE POLYETHYLENE 1811
	PLASTIC TENITE POLYETHYLENE 183H
	PLASTIC TENITE POLYETHYLENE 183M
	PLASTIC TENITE POLYETHYLENE 1840
	PLASTIC TENITE POLYETHYLENE 184L
	PLASTIC TENITE POLYETHYLENE 184M
	PLASTIC TENITE POLYETHYLENE 1870

MANUFACTURER	DESIGNATION
EASTMAN CHEMICAL PRODUCTS INC	PLASTIC TENITE POLYETHYLENE 18B0
	PLASTIC TENITE POLYETHYLENE 1924P
	PLASTIC TENITE POLYETHYLENE 1925F
	PLASTIC TENITE POLYETHYLENE 1930
	PLASTIC TENITE POLYETHYLENE 800
	PLASTIC TENITE POLYETHYLENE 808
	PLASTIC TENITE POLYETHYLENE 811
	PLASTIC TENITE POLYETHYLENE E6838-735
	PLASTIC TENITE POLYETHYLENE E6838-768F
	PLASTIC TENITE POLYETHYLENE E6838-781F
	PLASTIC TENITE POLYETHYLENE E6838-793F
	PLASTIC TENITE POLYETHYLENE E6838-807F
	PLASTIC TENITE POLYETHYLENE E6838-849P
	PLASTIC TENITE POLYETHYLENE E6838-868F
	PLASTIC TENITE POLYETHYLENE E6838-913P
	PLASTIC TENITE POLYETHYLENE E6838-914P
	PLASTIC TENITE POLYPROPYLENE 1550P
	PLASTIC TENITE POLYPROPYLENE 1924P
	PLASTIC TENITE POLYPROPYLENE 4220
	PLASTIC TENITE POLYPROPYLENE 4230
	PLASTIC TENITE POLYPROPYLENE 4231
	PLASTIC TENITE POLYPROPYLENE 4232
	PLASTIC TENITE POLYPROPYLENE 4242
	PLASTIC TENITE POLYPROPYLENE 4250
	PLASTIC TENITE POLYPROPYLENE 4531
	PLASTIC TENITE POLYPROPYLENE 4532
	PLASTIC TENITE POLYPROPYLENE 4E11
	PLASTIC TENITE POLYPROPYLENE 4E31
	PLASTIC TENITE POLYPROPYLENE 4E3V
	PLASTIC TENITE POLYPROPYLENE 4G7DP
	PLASTIC TENITE POLYPROPYLENE 4K31
	PLASTIC TENITE POLYPROPYLENE 4K32
	PLASTIC TENITE POLYPROPYLENE 4L31
	PLASTIC TENITE POLYPROPYLENE 4M40
	PLASTIC TENITE POLYPROPYLENE 4P31
	PLASTIC TENITE POLYPROPYLENE 4P32
	PLASTIC TENITE POLYPROPYLENE 808P
	PLASTIC TENITE POLYPROPYLENE E7-467P
	PLASTIC TENITE POLYPROPYLENE E8-849P
	PLASTIC TENITE POLYPROPYLENE E8-913P
	PLASTIC TENITE POLYPROPYLENE E8-914P
	PLASTIC TENITE POLYPROPYLENE H240
	PLASTIC TENITE POLYPROPYLENE P7673-469P
	PLASTIC TENITE POLYPROPYLENE P7673-499P
	PLASTIC TENITE POLYPROPYLENE P7673-607P
	PLASTIC TENITE POLYPROPYLENE P7673-648G
	PLASTIC TENITE POLYPROPYLENE P7673-780A
	PLASTIC TENITE POLYPROPYLENE P7673-940
	PLASTIC TENITE POLYPROPYLENE P7673-984
	PLASTIC TENITE POLYPROPYLENE P7673-996P
	PLASTIC TENITE POLYPROPYLENE R7673-930P
	PLASTIC TENITE PROPIONATE FORMULA 306 H
	PLASTIC TENITE PROPIONATE FORMULA 306 H2
	PLASTIC TENITE PROPIONATE FORMULA 306 H3
	PLASTIC TENITE PROPIONATE FORMULA 306 H4

MSFC-HDBK-527 REV F 9999942 0006889 3

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
EASTMAN CHEMICAL PRODUCTS INC	PLASTIC TENITE PROPIONATE FORMULA 306 H5
	PLASTIC TENITE PROPIONATE FORMULA 306 H6
	PLASTIC TENITE PROPIONATE FORMULA 306 MH
	PLASTIC TENITE PROPIONATE FORMULA 309 H2
	PLASTIC TENITE PROPIONATE FORMULA 309 H3
	PLASTIC TENITE PROPIONATE FORMULA 309 H4
	PLASTIC TENITE PROPIONATE FORMULA 309 H5
	PLASTIC TENITE PROPIONATE FORMULA 309 H6
	PLASTIC TENITE PROPIONATE FORMULA 311 H2
	PLASTIC TENITE PROPIONATE FORMULA 311 H3
	PLASTIC TENITE PROPIONATE FORMULA 311 H4
	PLASTIC TENITE PROPIONATE FORMULA 311 H5
	PLASTIC TENITE PROPIONATE FORMULA 311 H6
	PLASTIC TENITE PROPIONATE FORMULA 319 H2
	PLASTIC TENITE PROPIONATE FORMULA 319 H3
	PLASTIC TENITE PROPIONATE FORMULA 319 H4
	PLASTIC TENITE PROPIONATE FORMULA 319 H5
	PLASTIC TENITE PROPIONATE FORMULA 319 H6
	PLASTIC TENITE PROPIONATE FORMULA 325 H
	PLASTIC TENITE PROPIONATE FORMULA 325 H2
	PLASTIC TENITE PROPIONATE FORMULA 325 H3
	PLASTIC TENITE PROPIONATE FORMULA 325 H4
	PLASTIC TENITE PROPIONATE FORMULA 325 H5
	PLASTIC TENITE PROPIONATE FORMULA 325 H6
	PLASTIC TENITE PROPIONATE FORMULA 325 MH
	PLASTIC TENITE PROPIONATE FORMULA 326 H2
	PLASTIC TENITE PROPIONATE FORMULA 326 H3
	PLASTIC TENITE PROPIONATE FORMULA 326 H4
	PLASTIC TENITE PROPIONATE FORMULA 326 H5
	PLASTIC TENITE PROPIONATE FORMULA 326 H6
	PLASTIC TENITE PROPIONATE FORMULA 327 H
	PLASTIC TENITE PROPIONATE FORMULA 327 H2
	PLASTIC TENITE PROPIONATE FORMULA 327 H3
	PLASTIC TENITE PROPIONATE FORMULA 327 H4
	PLASTIC TENITE PROPIONATE FORMULA 327 H5
	PLASTIC TENITE PROPIONATE FORMULA 327 H6
	PLASTIC TENITE PROPIONATE FORMULA 327 MH
	PLASTIC TENITE PROPIONATE FORMULA 333 H
	PLASTIC TENITE PROPIONATE FORMULA 333 H2
	PLASTIC TENITE PROPIONATE FORMULA 333 H3
	PLASTIC TENITE PROPIONATE FORMULA 333 H4
	PLASTIC TENITE PROPIONATE FORMULA 333 H5
	PLASTIC TENITE PROPIONATE FORMULA 333 H6
	PLASTIC TENITE PROPIONATE FORMULA 333 M
	PLASTIC TENITE PROPIONATE FORMULA 333 MH
	PLASTIC TENITE PROPIONATE FORMULA 338 H
	PLASTIC TENITE PROPIONATE FORMULA 338 H2
	PLASTIC TENITE PROPIONATE FORMULA 338 H3
	PLASTIC TENITE PROPIONATE FORMULA 338 H4
	PLASTIC TENITE PROPIONATE FORMULA 338 H5
	PLASTIC TENITE PROPIONATE FORMULA 338 H6
	PLASTIC TENITE PROPIONATE FORMULA 338 MH
	PLASTIC TENITE PROPIONATE FORMULA 350 H2
	PLASTIC TENITE PROPIONATE FORMULA 350 H4
	PLASTIC TENITE PROPIONATE FORMULA 350 H5
	PLASTIC TENITE PROPIONATE FORMULA 350 H6
	PLASTIC TENITE PROPIONATE FORMULA 353 H
	PLASTIC TENITE PROPIONATE FORMULA 353 H2
	PLASTIC TENITE PROPIONATE FORMULA 353 H3
	PLASTIC TENITE PROPIONATE FORMULA 353 H4
	PLASTIC TENITE PROPIONATE FORMULA 353 H5
	PLASTIC TENITE PROPIONATE FORMULA 353 H6
	PLASTIC TENITE PROPIONATE FORMULA 353 M
	PLASTIC TENITE PROPIONATE FORMULA 353 MH
	PLASTIC TENITE PROPIONATE FORMULA 353 MS
	PLASTIC TENITE PROPIONATE FORMULA 353 S
	PLASTIC TENITE PROPIONATE FORMULA 353 S2
	PLASTIC TENITE PROPIONATE FORMULA 354 H2
	PLASTIC TENITE PROPIONATE FORMULA 354 H3
	PLASTIC TENITE PROPIONATE FORMULA 358 H2
	PLASTIC TENITE PROPIONATE FORMULA 358 H3
	PLASTIC TENITE PROPIONATE FORMULA 358 H4
	PLASTIC TENITE PROPIONATE FORMULA 358 H5
	PLASTIC TENITE PROPIONATE FORMULA 358 H6
EASTMAN KODAK	ADHESIVE A110
	ADHESIVE A148
	ADHESIVE A167
	ADHESIVE A298
	ADHESIVE A3
	ADHESIVE A32
	ADHESIVE A33
	ADHESIVE A337
	ADHESIVE A381
	ADHESIVE A383
	ADHESIVE A39
	ADHESIVE A40
	ADHESIVE A41
	ADHESIVE A43
	ADHESIVE A435
	ADHESIVE A475
	ADHESIVE A517
	ADHESIVE A525
	ADHESIVE A527
	ADHESIVE A528
	ADHESIVE A596
	ADHESIVE A604
	ADHESIVE A605
	ADHESIVE A620
	ADHESIVE A621
	ADHESIVE A630
	ADHESIVE A8
	ADHESIVE EASTMAN 901
	ADHESIVE G92
	ADHESIVE M336
	ADHESIVE M500
	BATTERY SUPRALIFE GOLD TIPPED KAA4 SIZE AA
	COATING KODAK REFLECTIVE WHITE
	FILM 2481 INFRARED (135-36)
	FILM EKTACHROME 200
	FILM EKTACHROME EE2241 (4001)

MSFC-HDBK-527 REV F 9999942 0006890 T

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
EASTMAN KODAK	FILM EKTACHROME SO251 HIGH SPEED VIDEO NEWS
	FILM EKTACHROME VIDEO NEWS
	FILM EKTACHROME VIDEO TY 4250
	FILM EKTAPRINT ON E20 PAPER
	FILM EKTRACHROME 5020
	FILM KODACHROME 64 KR135-36
	FILM KODACOLOR VR-G
	FILM KODACOLOR VR/1000
	FILM KODAK 160 COLOR MOVIE
	FILM KODAK 7294 HIGH SPEED
	FILM KODAK PCF135-36 STYLE2483
	FILM KODAK TX135-36
	FILM PANATONIC X/ACETATE
	FILM PANATONIC X3400/ESTAR
	FILM PHOTO EKTACHROME QX851
	FILM PHOTO LP4
	FILM PHOTO LP7
	FILM PHOTO PAN 2415
	FILM PHOTOGRAPHIC
	FILM PHOTOMICROGRAPHIC COLOR
	FILM VERLCULOR VPS488 TYPE S
	FILTER WRATTEN GELATIN 29
	INK KODAK 250/JCP E20 PAPER
	LABEL MARKING RC 55 PAPER
	MOLD COMPOUND POLYETHYLENE
	PAPER PHOTO 74 RC EKTACOLOR
	PAPER PHOTO 78 PLUS F COLOR PRINT MATERIAL
	PLASTIC POLYPROPYLENE 4231A
	PLASTIC TENITE BUTYRATE FORMULA H COMPRESSION
	PLASTIC TENITE BUTYRATE FORMULA H3 COMPRESSION
	PLASTIC TENITE POLYETHYLENE 1572
	PLASTIC TENITE POLYPROPYLENE
	PLASTIC TENITE POLYPROPYLENE 422D
	PLASTIC TENITE POLYPROPYLENE 4231E
	PLASTIC TENITE POLYPROPYLENE 4232A
	PLASTIC TENITE POLYPROPYLENE 4240
	PLASTIC TENITE POLYPROPYLENE 4250E
	PLASTIC TENITE POLYPROPYLENE 425A
	PLASTIC TENITE POLYPROPYLENE 4J31
	PLASTIC TENITE POLYPROPYLENE 4J32
	PLASTIC TENITE POLYPROPYLENE 4M40A
	PLASTIC TENITE POLYPROPYLENE 5250G
	PLASTIC TENITE PROPIONATE 338 FLOW H6 COMPRESSION
	PLASTIC TENITE PROPIONATE 338 FLOW H6 INJECTION
	PLASTIC TENITE PROPIONATE 350 FLOW H3 COMPRESSION
	PLASTIC TENITE PROPIONATE 350 FLOW H3 INJECTION
	PLASTIC TENITE PROPIONATE 358 FLOW H COMPRESSION
EASTMAN KODAK	PLASTIC TENITE PROPIONATE 358 FLOW H INJECTION
EBERHARD FABER	ERASER RUBBER PINK PEARL
ECC PRODUCTS	TUBING VITON HST
EDDINGTON THREAD	THREAD NYLON
	THREAD NYLON (ALL TYPES)
	THREAD NYLON NON-MELTING NOMEX
	THREAD NYLON VT295 SIZE E
	THREAD TEFLON S302 SIZE B
EDMONT WILSON	GLOVE VINYL DISPOSABLE 25165
	INSULATION FOAM TEMPERFOAM C42
	INSULATION FOAM TEMPERFOAM T38
	INSULATION FOAM TEMPERFOAM T41
EDWARD AFB	PAPER MAPS JCP E-20
EH33	COMPOSITE NEOPRENE/NOMEX HT337
	COMPOSITE NEOPRENE/POLYESTER
	RUBBER VITON RA61375VC
EH34	FABRIC NYLON/VITON
	FABRIC NYLON/VITON/ACHESON+500
	FABRIC NYLON/VITON/FLUOREL
EL PASO PRODUCTS	PLASTIC P1185A
	PLASTIC PE 102
	PLASTIC PE 103
	PLASTIC PE 107
	PLASTIC PE 108
	PLASTIC PE 109
	PLASTIC PE 118
	PLASTIC PE 119
	PLASTIC PE 121
	PLASTIC PE 122
	PLASTIC PE 125
	PLASTIC PE 126
	PLASTIC PE 127
	PLASTIC PE 128
	PLASTIC PE 142
	PLASTIC PE 143
	PLASTIC PE 171
	PLASTIC PE 172
	PLASTIC PE 178
	PLASTIC PE 179
	PLASTIC PE 181
	PLASTIC PE 200
	PLASTIC PE 202
	PLASTIC PE 204
	PLASTIC PE 204C5239
	PLASTIC PE 204C595
	PLASTIC PE 207
	PLASTIC PE 211
	PLASTIC PE 216
	PLASTIC PE 220
	PLASTIC PE 256
	PLASTIC PE101
	PLASTIC PE106
	PLASTIC PE111
	PLASTIC PP11512A

MSFC-HDBK-527 REV F 9999942 0006891 1

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
EL PASO PRODUCTS	PLASTIC PP11530V
	PLASTIC PP1154A
	PLASTIC PP11B12A
	PLASTIC PP11B30V
	PLASTIC PP11C8A
	PLASTIC PP11N12A
	PLASTIC PP11S20U
	PLASTIC PP13510A
	PLASTIC PP13N5A
	PLASTIC PP13R9A
	PLASTIC PP13T10A
	PLASTIC PP1452A
	PLASTIC PP1454A
	PLASTIC PP1455A
	PLASTIC PP1456A
	PLASTIC PP14B12A
	PLASTIC PP14C5A
	PLASTIC PP1752A
	PLASTIC PP1753A
	PLASTIC PP1754A
	PLASTIC PP1756A
	PLASTIC PP17C20A
	PLASTIC PP17C20A (XO-70/XO-76)
	PLASTIC PP17C6A
	PLASTIC PP1852A
	PLASTIC PP1853A
	PLASTIC PP1856A
	PLASTIC PP2352
	PLASTIC PP2352A
	PLASTIC PP23B2
	PLASTIC PP23B2A
	PLASTIC PP23M2
	PLASTIC PP23M2CS219
	PLASTIC PP23T2A
	PLASTIC PP24T2A
	PLASTIC PP3152A
	PLASTIC PP31530V
	PLASTIC PP3153A
	PLASTIC PP3154A
	PLASTIC PP4152A
	PLASTIC PP4154A
	PLASTIC PP41E2
	PLASTIC PP41E4
	PLASTIC PP41J7A
	PLASTIC PP43J4A
	PLASTIC PP4453A
	PLASTIC REXENE PE147
	PLASTIC REXENE PP11520V
	PLASTIC REXENE PP14S2A
	PLASTIC REXENE PP31SA
	PLASTIC XO-712
	PLASTIC XO-719
	PLASTIC XO-754
ELECTRO TECH	ADHESIVE POLYESTER ETC1
ELECTROFILM	LUBE DRY ELECTROFILM 1000 MOS2
ELECTROFILM	LUBE DRY ELECTROFILM 2006 ORG
	LUBE DRY ELECTROFILM 2306 INORGANIC
	LUBE DRY ELECTROFILM 4306
	LUBE DRY LUBELOK 5306
	LUBE DRY LUBELOK 66C FILM
	LUBE DRY LUBRIBOND 220 FILM
	LUBE DRY LUBRIBOND 320
	LUBE DRY LUBRIBOND A
	LUBE DRY LUBRIBOND HT MOS2/ST
	LUBE DRY MOLYKOTE 3402 MOS2
ELIZABETH WEBBING CO	STREAMER WARNING COTTON
ELL-BEE CHEMICAL CO	COATING ENAMEL 15251A WHITE
ELMHURST RUBBER CO	SPONGE RUBBER NEOPRENE
ELMORE CORP	THREAD NOMEX 50/3 TYPE 450
	THREAD NOMEX E77701/450 ROYAL BLUE SIZE 3/64
	THREAD NYLON SIZE E OLIVE DRAB
ELTON LEATHER CORP	LEATHER DEERSKIN
EMERSON AND CUMING	ADHESIVE ECCOBOND 104 EPOXY
	ADHESIVE ECCOBOND 104/ALUMINA
	ADHESIVE ECCOBOND 144B
	ADHESIVE ECCOBOND 1760
	ADHESIVE ECCOBOND 1765
	ADHESIVE ECCOBOND 24
	ADHESIVE ECCOBOND 26
	ADHESIVE ECCOBOND 27
	ADHESIVE ECCOBOND 276
	ADHESIVE ECCOBOND 276/C17
	ADHESIVE ECCOBOND 281
	ADHESIVE ECCOBOND 285-1
	ADHESIVE ECCOBOND 285-2
	ADHESIVE ECCOBOND 285-3
	ADHESIVE ECCOBOND 285/11 EPOXY
	ADHESIVE ECCOBOND 285/24LV EPOXY
	ADHESIVE ECCOBOND 3-2-5C
	ADHESIVE ECCOBOND 45
	ADHESIVE ECCOBOND 45/C15
	ADHESIVE ECCOBOND 45LV
	ADHESIVE ECCOBOND 51
	ADHESIVE ECCOBOND 51/C11
	ADHESIVE ECCOBOND 51/C9 EPOXY
	ADHESIVE ECCOBOND 55/C9
	ADHESIVE ECCOBOND 56/C11
	ADHESIVE ECCOBOND 56C EPOXY
	ADHESIVE ECCOBOND 56C/C9
	ADHESIVE ECCOBOND 59C/C59C
	ADHESIVE ECCOBOND 60C
	ADHESIVE ECCOBOND 60L
	ADHESIVE ECCOBOND 64C
	ADHESIVE ECCOBOND 64C1
	ADHESIVE ECCOBOND 66C EPOXY
	ADHESIVE ECCOBOND 70C EPOXY
	ADHESIVE ECCOBOND 787 A/B EPOXY
	ADHESIVE ECCOBOND 83C EPOXY
	ADHESIVE ECCOBOND 87H(NF)

MSFC-HDBK-527 REV F 9999942 0006892 3

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
EMERSON AND CUMING	ADHESIVE ECCOBOND 91/C11
	ADHESIVE ECCOBOND 91/C23LV
	ADHESIVE ECCOBOND 91/C9
	ADHESIVE ECCOBOND SF40
	ADHESIVE ECCOBOND SOLDER 57C
	ADHESIVE ECCOBOND SOLDER 58
	ADHESIVE ECCOBOND SOLDER V91
	ADHESIVE ECCOFOAM EFF14
	ADHESIVE ECCOFOAM FPH12-4H
	ADHESIVE ECCOLITE 82EP-PB
	ADHESIVE ECCOLITE 82SI-RS
	ADHESIVE ECCOPRIME S11
	ADHESIVE ECCOSHIELD VY-NC
	ADHESIVE ECCOSHIELD VY-NN
	ADHESIVE ECCOSHIELD VY81
	ADHESIVE ECCOSIL 1745
	ADHESIVE ECCOSIL 4553 RUBBER
	ADHESIVE ECCOSIL 4640
	ADHESIVE ECCOSIL 4712
	ADHESIVE ECCOSIL 4850
	ADHESIVE ECCOSIL 4952
	ADHESIVE ECCOSIL 4952/50
	ADHESIVE ECCOSIL GEL
	ADHESIVE ECCOSIL TP50
	ADHESIVE ECCOSIL W191C11/S11
	ADHESIVE ECCOSORB CR3 IRON/SILICONE RUBBER
	ADHESIVE ECCOSORB MF-S
	ADHESIVE ECCOSORB MF-S124
	ADHESIVE ECCOSORB RF/HT99
	ADHESIVE ECCOSORB VHP
	ADHESIVE STYCAST 2662/C14
	ADHESIVE STYCAST 2741/C15
	ADHESIVE STYCAST 3020
	ADHESIVE UV153
	ADHESIVE UV210
	ADHESIVE UV300
	ADHESIVE UV307
	ADHESIVE UV448
	ADHESIVE UV450
	ADHESIVE UV900
	ADHESIVE UV906
	ADHESIVE UV913
	COATING EC766 NITRILE/PHENOL
	COATING ECCOCOAT EC 210
	COATING ECCOCOAT EC D35
	ECCOGEL 1265/CABOSIL
	ECCOGEL 1265/EPOXY
	FILLER MATERIAL ECCOSPHERES SI
	INSULATION FOAM CPR488/ECCOBOND 59K ADHES
	INSULATION FOAM CPR488/ECCOBOND 60L ADHES
	INSULATION FOAM ECCOFOAM 12-2H
	INSULATION FOAM ECCOFOAM FPH 12-6H POLYURETHANE
	INSULATION FOAM ECCOFOAM FPH POLYURETHANE
	INSULATION FOAM ECCOFOAM FPH/FC721 COATED

MANUFACTURER	DESIGNATION
EMERSON AND CUMING	INSULATION FOAM ECCOFOAM TYPE SH
	LUBE GREASE ECCOTHERM TC4
	PLASTIC ECCOFOAM PS
	PLASTIC ECCOGEL 1365
	PLASTIC ECCOGEL 1365-12
	PLASTIC ECCOGEL 1365-25
	PLASTIC ECCOGEL 1365-35
	PLASTIC ECCOGEL 1365-45
	PLASTIC ECCOGEL 1365-65
	PLASTIC ECCOGEL 1365-80
	PLASTIC ECCOGEL 1365-9
	PLASTIC ECCOGEL 1365-90
	PLASTIC ECCOSEAL 1207
	PLASTIC ECCOSEAL W19
	PLASTIC ECCOSEAL W28G
	PLASTIC ECCOSEAL W67
	PLASTIC ECCOSHIELD CLV
	PLASTIC ECCOSHIELD SV
	PLASTIC STYCAST 1267
	PLASTIC STYCAST 1269A
	PLASTIC STYCAST 1495
	PLASTIC STYCAST 2057
	PLASTIC STYCAST 2058
	PLASTIC STYCAST 2651-1
	PLASTIC STYCAST 2651-40
	PLASTIC STYCAST 2651MM-1
	PLASTIC STYCAST 2750FR-N
	PLASTIC STYCAST 2760
	PLASTIC STYCAST 2850MT
	PLASTIC STYCAST 2851FT
	PLASTIC STYCAST 2851KT
	PLASTIC STYCAST 2851MT
	PLASTIC STYCAST 3020SC
	PLASTIC STYCAST 3180M
	POTTING COMPOUND STYCAST 1090 FR
	POTTING COMPOUND STYCAST 1090/C9
	POTTING COMPOUND STYCAST 1095/17 EPOXY
	POTTING COMPOUND STYCAST 1266
	POTTING COMPOUND STYCAST 1467
	POTTING COMPOUND STYCAST 1970
	POTTING COMPOUND STYCAST 2641-40/C9
	POTTING COMPOUND STYCAST 2651/C11
	POTTING COMPOUND STYCAST 2651/C9
	POTTING COMPOUND STYCAST 2651/C9 TOX RATE STUDY
	POTTING COMPOUND STYCAST 2651MM EPOXY
	POTTING COMPOUND STYCAST 2762/17
	POTTING COMPOUND STYCAST 2850FT/C11
	POTTING COMPOUND STYCAST 2850FT/C9
	POTTING COMPOUND STYCAST 2850GT/24LV
	POTTING COMPOUND STYCAST 2850GT/24LV TOX RATE STUDY
	POTTING COMPOUND STYCAST 2850GT/C11
	POTTING COMPOUND STYCAST 2850GT/C9
	POTTING COMPOUND STYCAST 2850KT/24LV

MSFC-HDBK-527 REV F 9999942 0006893 5

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
EMERSON AND CUMING	POTTING COMPOUND STYCAST 2850KT/C11
	POTTING COMPOUND STYCAST 2850KT/C9
	POTTING COMPOUND STYCAST 3050/C9
	RUBBER ECCOTHANE 7510
	RUBBER ECCOTHANE CPC18
	RUBBER ECCOTHANE CPC19
	RUBBER ECCOTHANE CPC39
	RUBBER ECCOTHANE CPC41
EMERY CHEMICALS	PLASTIC PLASTOLEIN 9050
	PLASTIC PLASTOLEIN 9058
	PLASTIC PLASTOLEIN 9065
	PLASTIC PLASTOLEIN 907
	PLASTIC PLASTOLEIN 9091
	PLASTIC PLASTOLEIN 9215
	PLASTIC PLASTOLEIN 9232
	PLASTIC PLASTOLEIN 9250
	PLASTIC PLASTOLEIN 9404
	PLASTIC PLASTOLEIN 9717
	PLASTIC PLASTOLEIN 9720
	PLASTIC PLASTOLEIN 9731
	PLASTIC PLASTOLEIN 9752
	PLASTIC PLASTOLEIN 9756
	PLASTIC PLASTOLEIN 9761
	PLASTIC PLASTOLEIN 9762
	PLASTIC PLASTOLEIN 9765
	PLASTIC PLASTOLEIN 9776
	PLASTIC PLASTOLEIN 9783
	PLASTIC PLASTOLEIN 9789
	PLASTIC PLASTOLEIN 9790
EMSER INDUSTRIES	ADHESIVE GRILTEX 1G
	ADHESIVE GRILTEX 2G
	ADHESIVE GRILTEX 4G
	ADHESIVE GRILTEX 5G
	ADHESIVE GRILTEX 6G
	ADHESIVE GRILTEX 8G
	PLASTIC GRILAMID L16GM
	PLASTIC GRILAMID L20G
	PLASTIC GRILAMID L20W20
	PLASTIC GRILAMID L20W40
	PLASTIC GRILAMID L25
	PLASTIC GRILAMID L25W40
	PLASTIC GRILAMID L25W40NZ NYLON 12
	PLASTIC GRILAMID LKN5H
	PLASTIC GRILAMID LV3H
	PLASTIC GRILAMID LV43H
	PLASTIC GRILAMID TR55
	PLASTIC GRILAMID TR55LX
	PLASTIC GRILAMID TR55UV
	PLASTIC GRILAMID W2291 NYLON 12
	PLASTIC GRILAMID W5941
	PLASTIC GRILAMID W6923
	PLASTIC GRILAN A28GM
	PLASTIC GRILON A23G NAT 6165
	PLASTIC GRILON A23GM
	PLASTIC GRILON A28GM
EMSER INDUSTRIES	PLASTIC GRILON A28NX
	PLASTIC GRILON A28NY
	PLASTIC GRILON A28NZ
	PLASTIC GRILON A28VO
	PLASTIC GRILON BT40
	PLASTIC GRILON CA6E
	PLASTIC GRILON CR9
	PLASTIC GRILON F40
	PLASTIC GRILON F47
	PLASTIC GRILON F50
	PLASTIC GRILON PV3H
	PLASTIC GRILON PVN154
	PLASTIC GRILON PVN3H
	PLASTIC GRILON R40
	PLASTIC GRILON R40GM
	PLASTIC GRILON R47HW
	PLASTIC GRILON W3941
	PLASTIC GRILON W5744
ENDEVCO	WIRE ELEC FEP/POLYIMIDE TAPE
ENFIELD INDUSTRY	TUBING DURAPLUS ABS
ENGINEERED DEVICES	COATING TEFLON INFUSED
ENGINEERING PLASTICS	PLASTIC LEXAN 2014 POLYCARBONATE
ENGLISH LEATHER	DEODORANT ENGLISH LEATHR SOLID
ENVIROPAK INC	FABRIC DRIGUARD 1227 NYLON/PVC
	FABRIC DRIGUARD 1527 POLYESTER
EON CORP	LACING TAPE NYLON 17X POLYAMID
	LACING TAPE POLYESTER AIR-TEX 217
EPD INDUSTRIES	BAG ZIP LOCK VINYL ACETATE
EPOXY TECHNOLOGY	ADHESIVE EPOTEK
	ADHESIVE EPOTEK 301 EPOXY
	ADHESIVE EPOTEK 301-2
	ADHESIVE EPOTEK 302
	ADHESIVE EPOTEK 310
	ADHESIVE EPOTEK 320
	ADHESIVE EPOTEK 330
	ADHESIVE EPOTEK 331
	ADHESIVE EPOTEK 353 EPOXY
	ADHESIVE EPOTEK 353ND
	ADHESIVE EPOTEK 360
	ADHESIVE EPOTEK 360ST
	ADHESIVE EPOTEK 360T
	ADHESIVE EPOTEK 390
	ADHESIVE EPOTEK 394
	ADHESIVE EPOTEK 410E
	ADHESIVE EPOTEK 415G
	ADHESIVE EPOTEK 444
	ADHESIVE EPOTEK 454
	ADHESIVE EPOTEK 877
	ADHESIVE EPOTEK 905
	ADHESIVE EPOTEK H205
	ADHESIVE EPOTEK H20E175
	ADHESIVE EPOTEK H20S
	ADHESIVE EPOTEK H21D
	ADHESIVE EPOTEK H22
	ADHESIVE EPOTEK H27D

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006894 7

MANUFACTURER	DESIGNATION
EPOXY TECHNOLOGY	ADHESIVE EPOTEK H31
	ADHESIVE EPOTEK H31D
	ADHESIVE EPOTEK H31LV
	ADHESIVE EPOTEK H40
	ADHESIVE EPOTEK H41
	ADHESIVE EPOTEK H43
	ADHESIVE EPOTEK H55
	ADHESIVE EPOTEK H61
	ADHESIVE EPOTEK H62
	ADHESIVE EPOTEK H70E EPOXY
	ADHESIVE EPOTEK H70E4
	ADHESIVE EPOTEK H70S
	ADHESIVE EPOTEK H72 EPOXY
	ADHESIVE EPOTEK H74
	ADHESIVE EPOTEK H77
	ADHESIVE EPOTEK H81
	ADHESIVE EPOTEK H81E
	ADHESIVE EPOTEK P10
	ADHESIVE EPOTEK P1011
EPOXYLITE CORP	ADHESIVE BR104 EPOXY
	ADHESIVE BR22
	ADHESIVE EPOXYLITE 1462
	ADHESIVE EPOXYLITE 203
	ADHESIVE EPOXYLITE 211/C383
	ADHESIVE EPOXYLITE 221/C307
	ADHESIVE EPOXYLITE 223
	ADHESIVE EPOXYLITE 3101
	ADHESIVE EPOXYLITE 3351
	ADHESIVE EPOXYLITE 5302
	ADHESIVE EPOXYLITE 5403 EPOXY
	ADHESIVE EPOXYLITE 5526
	ADHESIVE EPOXYLITE 6001 COATING
	ADHESIVE EPOXYLITE 6203 COATING
	ADHESIVE EPOXYLITE 801-45 EPOXY
	ADHESIVE EPOXYLITE 801/C307
	ADHESIVE EPOXYLITE 810
	ADHESIVE EPOXYLITE 813
	ADHESIVE EPOXYLITE 813-9 COATING
	ADHESIVE EPOXYLITE 8164
	ADHESIVE EPOXYLITE 8611
	ADHESIVE EPOXYLITE 8705
	ADHESIVE EPOXYLITE 8712 COATING
	ADHESIVE EPOXYLITE 8743
	ADHESIVE EPOXYLITE 8751
	ADHESIVE EPOXYLITE 8822
	ADHESIVE EPOXYLITE 8899
	ADHESIVE EPOXYLITE 8993
	ADHESIVE EPOXYLITE 9653 A/B EPOXY COATING
	ADHESIVE EPOXYLITE CF8628 COATING
	ADHESIVE EPOXYLITE CF8628 EP
	ADHESIVE PLD700
	LAMIN EPOXY/GLASS WITH EPOXYLITE 9653
	POTTING COMPOUND EPOXYLITE 210/C321
EPSCO INC	FLUOROGREEN E-600 TFE/GLASS
ERNO PRODUCTS	LUBE ERNO FV0163015
ERWIN CO	TAPE MEASURE ERWIN PC10
ESA	INSULATION FOAM PYRELL UNCOATED
	INSULATION FOAM PYRELL UNCOATED AND COATED
	RL4389
	WIRE ELEC REINSHAGEN POLYIMIDE
ESA/ERNO	BELLOWS/TUBE FLEXAFIT SG2212
	FABRIC SILICONE/GLASS GS200
	FOAM PYRELL FOAM/IN METAL TOOLBOX
	INSULATION FOAM ECCOFOAM 12-6H
	INSULATION FOAM PYRELL UNCOATED
	LENS MAKROLON 3900LS
	MULTI-LAYERED INSULATION GOLDIZED KAPTON
	PAPER NOMEX/HONEYCOMB
	REVAC DD2010
	TUBING FLEXAFIT SG2122
ESSELTE PENDAFLEX	INK 42-11FD MARKING BLACK
ESSEX CHEM CORP	ADHESIVE BETAMATE 435.71
	ADHESIVE BETAMATE 435.72
	ADHESIVE BETAMATE 435.81
	ADHESIVE BETAMATE 57.511/57.512 STRUCTURAL
	ADHESIVE BETAMATE 57.541/57.542 STRUCTURAL
	ADHESIVE BETASEAL 20-601
	ADHESIVE BETASEAL 550.02
	ADHESIVE BETASEAL 551.02
	ADHESIVE BETASEAL 553.02
	ADHESIVE BETASEAL XP01543C
	PAPER COPACO
	POTTING COMPOUND PROSEAL 799
	SEALANT PROSEAL 727-2-3 POLYSULFIDE
ESTEE LAUDER	EYE SHADOW CREME SKYLIGHT BLUE
ETHERINGTON/U S PROLAM	ADHESIVE E705
	ADHESIVE E710
	ADHESIVE E746
	ADHESIVE E760
	ADHESIVE E767
	ADHESIVE F502
	ADHESIVE P602
	ADHESIVE P650
	ADHESIVE P670I
	ADHESIVE P680
	ADHESIVE S860
ETHYL CORP	RUBBER EYPEL F4001
	RUBBER EYPEL F6504
	RUBBER EYPEL F7001
	RUBBER EYPEL F7003
	RUBBER EYPEL F7005
	RUBBER EYPEL F7509
	RUBBER EYPEL F8003
	RUBBER EYPEL F9003
EUCLID CHEMICAL	ADHESIVE EUCO 352 GEL
	ADHESIVE EUCO 352LV
	ADHESIVE EUCO 352MV
	ADHESIVE EUCO 452 GEL
	ADHESIVE EUCO 452LV
	ADHESIVE EUCO 452MV

MSFC-HDBK-527 REV F 9999942 0006895 9

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
EUCLID CHEMICAL	ADHESIVE EUCO 456 MORTAR
	ADHESIVE EUCO 456S
	ADHESIVE EUCO 460 GEL
	ADHESIVE EUCO 460LV
	ADHESIVE EUCO 460MV
	ADHESIVE EUCO 520 GEL
	ADHESIVE EUCO 520LV
	ADHESIVE EUCO 520MV
	ADHESIVE EUCO 620 GEL
	ADHESIVE EUCO 620LV
	ADHESIVE EUCO 620MV
	ADHESIVE EUCO M235 C1
	ADHESIVE EUCO M235 C2
	ADHESIVE EUCO PLASTISEAL
	ADHESIVE EUCO POLYSULFIDE SEALANT
	ADHESIVE EUCOPOXY LT
EUTSLER TECHNICAL PROD	RUBBER JAMAK 7176
	RUBBER NEOPRENE
	RUBBER SILICONE E6132
EVANS PRODUCTS	MOOG A22035 LUBRICANT
EVERLUBE	LUBE DRY EVERLUBE 1120-8
	LUBE DRY EVERLUBE 620C
	LUBE DRY EVERLUBE 811
	LUBE DRY EVERLUBE 823
	LUBE EVERLUBE 620A
	LUBE EVERLUBE 620B1
EXPANDED RUBBER	INSULATION FOAM NEOPRENE LS200
	INSULATION FOAM POLYURETHANE STATHANE G502 SE
	INSULATION FOAM TEMPERFOAM T47
	SPONGE RUBBER ENSOLITE AL PVC/NITRILE
EXXON	FILM CMC8-14-1A POLYIMIDE
	LUBE GREASE BEACON 325
	PLASTIC ESCORENE
	PLASTIC ESCORENE 1012
	PLASTIC ESCORENE 1024
	PLASTIC ESCORENE 1032
	PLASTIC ESCORENE 1042
	PLASTIC ESCORENE 1044
	PLASTIC ESCORENE 1052
	PLASTIC ESCORENE 1063
	PLASTIC ESCORENE 1074
	PLASTIC ESCORENE 1105
	PLASTIC ESCORENE 1154
	PLASTIC ESCORENE 1164
	PLASTIC ESCORENE 1172
	PLASTIC ESCORENE 1222F
	PLASTIC ESCORENE 1224F
	PLASTIC ESCORENE 1403F
	PLASTIC ESCORENE 1404F
	PLASTIC ESCORENE 2072
	PLASTIC ESCORENE 2082
	PLASTIC ESCORENE 2092
	PLASTIC ESCORENE 3014
	PLASTIC ESCORENE 3035

MANUFACTURER	DESIGNATION
EXXON	PLASTIC ESCORENE 3045
	PLASTIC ESCORENE 3114G
	PLASTIC ESCORENE 3125
	PLASTIC ESCORENE 3145
	PLASTIC ESCORENE 3235
	PLASTIC ESCORENE 3274
	PLASTIC ESCORENE 4023
	PLASTIC ESCORENE 4033
	PLASTIC ESCORENE 4062
	PLASTIC ESCORENE 4082
	PLASTIC ESCORENE 4092
	PLASTIC ESCORENE 4103
	PLASTIC ESCORENE 4134
	PLASTIC ESCORENE 4152
	PLASTIC ESCORENE 4162
	PLASTIC ESCORENE 4193
	PLASTIC ESCORENE 5022
	PLASTIC ESCORENE 5052
	PLASTIC ESCORENE 5141G
	PLASTIC ESCORENE 5164G
	PLASTIC ESCORENE 5181
	PLASTIC ESCORENE 7022
	PLASTIC ESCORENE 7032
	PLASTIC ESCORENE 7033
	PLASTIC ESCORENE 7034
	PLASTIC ESCORENE 8032
	PLASTIC ESCORENE 8042
	PLASTIC ESCORENE 8051
	PLASTIC ESCORENE 9012
	PLASTIC ESCORENE 9022
	PLASTIC ESCORENE 9032
	PLASTIC ESCORENE 9044
	PLASTIC ESCORENE LD-701
	PLASTIC ESCORENE LD-702
	PLASTIC LA102
	PLASTIC LA103
	PLASTIC LA104
	PLASTIC LA105
	PLASTIC LA106
	PLASTIC LA113
	PLASTIC LA117
	PLASTIC LA122
	PLASTIC LA124
	PLASTIC LA129
	PLASTIC LA130
	PLASTIC LA302
	PLASTIC LA305
	PLASTIC LA306
	PLASTIC LA307
	PLASTIC LA308
	PLASTIC LA309
	PLASTIC LA701
	PLASTIC LA702
	PLASTIC LA703
	PLASTIC LD100

MSFC-HDBK-527 REV F 9999942 0006896 0

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
EXXON	PLASTIC LD700
	PLASTIC XQ-32
	PLASTIC XQ-36
	PLASTIC XQ-43
	PLASTIC XQ-46
	RUBBER VISTANEX MML100 BUTYL
FABER CASTELL CORP	INK HIGGINS BLACK MAGIC WATERPROOF INDIA 4465
FABLOCK MILLS	FABRIC NYLON MESH 8885
	POLYPROPYLENE STYLE 9079
FABRIC DEVELOPMENT	FABRIC KELVAR 29
	FABRIC KEVLAR 152 KNIT
	FABRIC KEVLAR STYLE 202 3.2 OZ
	FABRIC KEVLAR STYLE FDI043
	FABRIC KEVLAR/NOMEX STYLE 145
	FABRIC ORTHO 116
	FABRIC POLYESTER KNIT
	SLEEVING DACRON WOVEN FABRIC
FABRIC RESEARCH LAB	ABLATOR MA-25/FRL-IV
	CORD KEVLAR/NOMEX
	CORD PBI STYLE S121
	FABRIC KELVAR 29
	FABRIC KEVLAR 2176
	FABRIC PBI
	FABRIC PBI FRL-73300-131
	FABRIC PBI FRL-73300-190 FX
	FABRIC PBI FRL-73300-196 FX
	FABRIC PBI FRL-73300-197
	FABRIC PBI FRL-73300-197 FX
	FABRIC PBI FRL-73300-201 FX
	FABRIC PBI S-141 FX WEBBING
	FABRIC PBI S-164 FX RASCHELNET
	FABRIC PBI S-165 FX
	FABRIC PBI S-210 FX 4.80Z/SQYD
	FABRIC POLYIMIDE FIBER
	FELT NOMEX 4.5 OZ/SQ YD
	FELT NOMEX NON-WOVEN
	INSULATION FOAM BX250 FRL COATED
	INSULATION FOAM GREAT STUFF WITH FRL-4
	INSULATION FOAM NCFI 22-65 WITH FRL4
	LACING TAPE 615-158-1
	LACING TAPE 615-158-3
	LACING TAPE 615-158-5
	LACING TAPE FRL 615-157 PBI
	LACING TAPE FRL 615-158 PBI
	LACING TAPE FRL 73300-130-5
	TAPE KEVLAR 2176-1
	TAPE LACING S199 POLYIMIDE
	THREAD PBI FRL-S152
	WEBBING KEVLAR FRL-S-196
	WEBBING KEVLAR FRL-S201
	WEBBING PBI FRL-S169 FX
	ZIPPER TFE/FIBERGLASS/NOMEX
FAFNIR BEARING	TUBING FAFTEX PTFE LINER
FAIRCHILD	TEFLON TFE VIRGIN
FASSON	TAPE FASTAPE A PS
FAUTLESS	RUBBER LATEX NATURAL
FEDERAL HOSE	HOSE FEDFLEX SGG
FEDERAL SUPPLY	POTTING COMPOUND NYLON BOOT
FEDERAL-MOGUL	RUBBER EPR AS014
	RUBBER EPR ORINGS NS014 E59
FEL PRO INC	ADHESIVE FELPRO GS1
	ADHESIVE FELPRO GS2
	ADHESIVE FELPRO GS3 SEALER
	ADHESIVE FELPRO HPS SEALER
	ADHESIVE FELPRO PROLOCK FLANGE SEALANT
	ADHESIVE FELPRO PROLOCK PIPE SEALANT
	LUBE FELPRO C100
FELTERS CO	FABRIC FELT 5913-07 NOMEX
FENWAL INC	ADHESIVE TRUCAST 111M
	ADHESIVE TRUCAST 111M/901 EPOXY
FERRO	LAMIN CE9020/120/45% RC
	LAMIN EPOXY/ARAMID
	LAMIN EPOXY/ARAMID F164
	LAMIN EPOXY/GLASS CE3201
	LAMIN EPOXY/GLASS CE9000
	LAMIN EPOXY/GLASS CE9010
	LAMIN EPOXY/GLASS CE9010/120
	LAMIN EPOXY/GLASS CE9010/181 KEVLAR 49
	LAMIN EPOXY/GLASS CE9010/7781 TOX RATE STUDY
	LAMIN EPOXY/GLASS CE9010A/120
	LAMIN EPOXY/GLASS CE9020/7781
	LAMIN EPOXY/GLASS CE9020/KEVLAR 49
	LAMIN EPOXY/GLASS CORDOPREG E293
	LAMIN EPOXY/KEVLAR CE306/281
	LAMIN EPOXY/KEVLAR CE9010/7781
	LAMIN EPOXY/PLASTIC
	LAMIN PHENOLIC 2210/A1100/1581
	LAMIN POLYIMIDE/GLASS CP2252/7781
	LAMIN POLYIMIDE/GLASS CPI2252/7781
FIBER-RESIN CORP	ADHESIVE CYCLEWELD
	ADHESIVE CYCLEWELD 5420A/640A
	ADHESIVE CYCLEWELD 55-9
	ADHESIVE CYCLEWELD C14
	ADHESIVE CYCLEWELD K114 A/B
	ADHESIVE FIBER RESIN 12/HARDENER 5
	ADHESIVE FIBER RESIN 12/HARDENER 6
	ADHESIVE FIBER RESIN 13
	ADHESIVE FIBER RESIN 3118 A/B
	ADHESIVE FIBER RESIN 337 POLYURETHANE
	ADHESIVE FIBER RESIN 5366 POLYURETHANE
	ADHESIVE FIBER RESIN 7010FR
	ADHESIVE FIBER RESIN 7011 POLYURETHANE
	ADHESIVE FIBER RESIN 7015-1 A/B
	ADHESIVE FIBER RESIN 7016
	ADHESIVE FIBER RESIN 7018 A/B
	ADHESIVE FIBER RESIN 7026
	ADHESIVE FIBER RESIN 7026 POLYURETHANE
	ADHESIVE FIBER RESIN 7030

MSFC-HDBK-527 REV F 9999942 0006897 2

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
FIBER-RESIN CORP	ADHESIVE FIBER RESIN 7031 POLYURETHANE
	ADHESIVE FIBER RESIN 7035 POLYURETHANE
	ADHESIVE FIBER RESIN 7037 POLYURETHANE
	ADHESIVE FIBER RESIN 7106 POLYURETHANE
	ADHESIVE FIBER RESIN 7136-2 POLYURETHANE
	ADHESIVE FIBER RESIN 7162 POLYURETHANE
	ADHESIVE FIBER RESIN 7171 POLYURETHANE
	ADHESIVE FIBER RESIN 7176 POLYURETHANE
	ADHESIVE FIBER RESIN 7179
	ADHESIVE FIBER RESIN 7182
	ADHESIVE FIBER RESIN 7183 A/B POLYURETHANE
	ADHESIVE FIBER RESIN 7332 POLYURETHANE
	ADHESIVE FIBER RESIN 7336 POLYURETHANE
	ADHESIVE FIBER RESIN 8193 A/B POLYURETHANE
	ADHESIVE FIBER RESIN 8194 A/B POLYURETHANE
	ADHESIVE FIBER RESIN 8503 POLYURETHANE
	ADHESIVE FIBER RESIN 8516
	ADHESIVE FR14/NO.5 HARDENER
	ADHESIVE FR14/NO.6 HARDENER
FIBERGLASS REIN INC	FABRIC FIBERGLASS STYLE 7628
FIBERITE	CONFIG SEE 06475/05325
	ELECTRICAL CONNECTOR WITH FIBERITE FM4051
	FABRIC CARBON PHENOLIC ABLATIVE
	GRAPHITE FIBERITE HMF EPOXY
	LAMIN EPOXY/GRAPHITE
	LAMIN EPOXY/GRAPHITE HE1034E
	LAMIN EPOXY/GRAPHITE HMF/34
	LAMIN EPOXY/GRAPHITE HMF330B/34
	LAMIN EPOXY/GRAPHITE T50/934
	LAMIN FIBERITE MXB5004/1581
	LAMIN FIBERITE MXB7701
	LAMIN FIBERITE T50/934 GRAPHITE WITH
	ADHESIVE FILM HT424 AND PRIMER
	LAMIN GRAPHITE/POLYIMIDE
	LAMIN HMS/934/SONA30 EPOXY
	LAMIN HMS/X904
	LAMIN THORNEL 300/934 GRAPHITE/EPOXY
	MOLD COMPOUND C2175 EPOXY
	MOLD COMPOUND E-21718/X49556
	MOLD COMPOUND E-21718/X49560
	MOLD COMPOUND E-2748 EPOXY/GLASS
	MOLD COMPOUND E-3938C GLASS/EPOXY
	MOLD COMPOUND FIBERITE FM-8130
	MOLD COMPOUND FIBERITE FM4005 BLACK
	MOLD COMPOUND FIBERITE FM4008
	MOLD COMPOUND FIBERITE FM4030-190
	MOLD COMPOUND M2840 MELAMINE
	PLASTIC E20328
	PLASTIC E2171 8X60
	PLASTIC E2171 8X61
	PLASTIC E2171 8X65
	PLASTIC E260H
	PLASTIC E261H
	PLASTIC E264H
	PLASTIC E2748-9641CB

MANUFACTURER	DESIGNATION
FIBERITE	PLASTIC E7300
	PLASTIC E8353
	PLASTIC E8354
	PLASTIC E8354-19189
	PLASTIC E8379
	PLASTIC E8382
	PLASTIC E8411
	PLASTIC E8414
	PLASTIC E8625
	PLASTIC E8636
	PLASTIC FM10365
	PLASTIC FM1303-8880
	PLASTIC FM16771
	PLASTIC FM21288
	PLASTIC FM3000
	PLASTIC FM3001
	PLASTIC FM3002
	PLASTIC FM32168
	PLASTIC FM32175
	PLASTIC FM32780
	PLASTIC FM3510
	PLASTIC FM4002
	PLASTIC FM4004
	PLASTIC FM4005 X 4648
	PLASTIC FM4005F
	PLASTIC FM4007
	PLASTIC FM4009
	PLASTIC FM4011
	PLASTIC FM4024
	PLASTIC FM4029F
	PLASTIC FM4036
	PLASTIC FM4055
	PLASTIC FM4056
	PLASTIC FM4060
	PLASTIC FM4070
	PLASTIC FM4555
	PLASTIC FM50501
	PLASTIC FM5064
	PLASTIC FM5085
	PLASTIC FM510
	PLASTIC FM5367
	PLASTIC FM6030
	PLASTIC FM8130E
	PLASTIC FM8720
	PLASTIC FM9294
	PLASTIC M2014
	PLASTIC M2037
	PLASTIC M6204
	PLASTIC PI730
	PLASTIC PI740
	PLASTIC PI745
	PLASTIC PI750
	PLASTIC S660
	PLASTIC S680
	PLASTIC S690

MSFC-HDBK-527 REV F 9999942 0006898 4

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
FIBERITE	PLASTIC S695
	PLASTIC S706
	PLASTIC S706M
	PLASTIC SI9002
	PLASTIC SI9041
	PLASTIC VE49595
	PLASTIC X28057
	POTTING COMPOUND E9405 EPOXY/GLASS
	POTTING COMPOUND FM1132 PHENOLIC
FIBERITE/US POLYMERIC	FABRIC MX2600/FM5504 SILICA PHENOLIC
	FABRIC MXB6020/FM5755 GLASS PHENOLIC
FIBERLAY INC	MOLD COMPOUND POLYESTER
FIBRE MATERIAL CORP	NYLATRON GS/GLASS FILLED NYLON
FILISTER	CABLE COAX SILVER PLATED COPPER WITH PTFE KAPTON
	TETRA-ETCH FLUOROCARBON
	WIRE ELEC 1871-2-169 PTFE KAPTON
	WIRE ELEC BTV 2-26-BF-9 PTFE KAPTON
	WIRE ELEC MTV TYPE/PTFE KAPTON INSULATION
FILLITE U S A INC	PLASTIC DMC
	PLASTIC FILLITE 100/7
	PLASTIC FILLITE 200/7
	PLASTIC FILLITE 300/7
	PLASTIC FILLITE 52/7/5
	PLASTIC FILLITE IN POLYESTER RESIN
	PLASTIC FILLITE M32
	PLASTIC FILLITE MICRO BALLONS
	PLASTIC FILLITE MICRO BALLONS IN EPOXY RESINS
	PLASTIC FILLITE P2000
	PLASTIC FILLITE PFA
	PLASTIC SMC
FIRE TECT	COATING LATEX VINYL WT102
	COATING PC210 FIRE RETARDANT
	INSULATION FOAM PYRELL PC210 COATING
FIRESAFE PRODUCTS	FABRIC DURETTE 400-11 NOMEX
	FABRIC DURETTE 400-11/7878 NOMEX
	FABRIC DURETTE 400-18 NOMEX HT
	FABRIC DURETTE 400-36 NOMEX
	FABRIC DURETTE 400-37 NOMEX HT
	FABRIC DURETTE 400-7 NOMEX HT
	FABRIC DURETTE 420-11
	FABRIC DURETTE 420-2
	FABRIC DURETTE 430-13
	FABRIC DURETTE HCO-2
	FABRIC FELT DURETTE BATTING
FIRESTONE	RUBBER PNF 225-001
	RUBBER PNF 240-001
	RUBBER PNF 260-004
	RUBBER PNF 265-003
	RUBBER PNF 265-004
	RUBBER PNF 270-001
	RUBBER PNF 270-003
	RUBBER PNF 270-003R ELASTOMER
	RUBBER PNF 275-006

MANUFACTURER	DESIGNATION
FIRESTONE	RUBBER PNF 275-009
	RUBBER PNF 280-003
	RUBBER PNF 280-008
	RUBBER PNF 280-009
	RUBBER PNF 285-005
	RUBBER PNF INORGANIC
	RUBBER POLYPHOSPHAZENE (PNF)
FISHER PEN	INK PEN 775SL SILVER MED-PT
	INK PEN SL SILVER BROAD POINT
	PEN AG-7 BLK MED POINT ANTI-G
	PEN FISHER SPACE REFILL P/N PR6 PURPLE MEDIUM POINT
	PEN FISHER SPACE REFILL P/N PR9 LIGHT BLUE MEDIUM POINT
	PEN SPACE B1-PR4F REFILL BLACK
FISHER SCIENTIFIC	CONNECTOR 15-319D
	INK PEN 60 SILVER
	LUBE OIL FLUOROLUBE LG160
	POLYSTYRENE PETRI DISH
	TUBING LATEX RUBBER
FISKE BROTHERS REFINING	GREASE LUBRIPLATE 130A
FLAMEMASTER CORP	COATING D65/TOPCOAT 904
	INSULATION FOAM POLYURETHANE
FLEXAUST	HOSE NEOPRENE CWC
FLEXCO	TILE FLEXCO A68 HW
	TILE FLEXCO C10 HW
	TILE FLEXCO SP40 HW
FLEXCRAFT IND	ADHESIVE FLEXCRAFT 868 URETHANE/VINYL
FLEXFAB	FABRIC DF513/DF202 SILICONE
	HOSE FLEX SILFAB-1 SIL/GL/FAB
	HOSE FLEX SILFAB-2 SIL/GL/FAB
	HOSE FLEX TURBOFAB FLUOROSILICONE
	HOSE NEOFAB-2 FLEX
FLEXFORMERS	MOLD COMPOUND POLYURETHANE CASTABLE
FLEXIBLE TUBING	TUBING VACUFLEX PVC HST
FLEXITHERM	FABRIC 100% COTTON KNIT JERSEY
FLEXOFILM	LABEL IDENTIFICATION FLEXOFILM CHROME MYLAR WITH NAZDAR MY111 BLACK INK WITH ACRYLIC PS V23 ADHESIVE
FLIGHT SUITS LTD	FABRIC NOMEX BLUE FLIGHT SUIT
FLIGHTEX FABRIC CO	FABRIC COTTON NATURAL
FLODYNE CONTROLS	RUBBER VITON FLUID RESISTANT
	RUBBER VITON V747-7
FLOW TECHNOLOGY	TEFLON TFE FILLED NOC
FLUID MECHANICS VALVE CO	VESPEL SP21
FLUID POWER	RUBBER NEOPRENE
	RUBBER VITON
FLUID POWER INC	RUBBER SILICONE CL 3B GR 70
FLUIDTRONICS INC	FLUIDTRONICS LIP SEAL
FLUORAMICS INC	LUBE GREASE OXY 8
FLUORGLAS	INSULATION BLANKET FLUORGLAS 385-3
FLUORO-PLASTICS	ADHESIVE 80
	ADHESIVE 85

MSFC-HDBK-527 REV F 9999942 0006899 6

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
FLUOROCARBON CORP	ADHESIVE FOMO 5-10
	ADHESIVE HANDIFOAM
	ADHESIVE HANDIFOAM 2
	FILM GORETEX 1/4" TFE PIPE SEALANT/ NONADHESIVE
	FILM TFE LPN123 GRAPHITE FILL
	FLUOROGOLD TFE/GLASS 25%
	FLUOROGOLD WITH GREEN PIGMENT
	FLUOROLOY B TFE/CARBON/GRAPHITE
	FLUOROLOY D
	FLUOROLOY F TFE/CERAMIC
	FLUOROLOY H TFE/BORON NITRATE
	FLUOROLOY K
	FLUOROLOY KP TFE/ECONOL
	FLUOROLOY S TFE/CD SE SULFIDE
	FLUOROLOY SL TEFLON/GRAPHITE
	KEL-F 6060
	KEL-F 6061-T6 10% GLASS
	KEL-F 81
	KEL-F 81/6060 RESIN
	KEL-F 81/6061 RESIN
	KEL-F CTFE UNPLASTICIZED
	PLASTIC FLUOROCARBON WAFER
	PLASTIC FLUOROGOLD
	PLASTIC FLUOROLOY A
	PLASTIC FLUOROLOY C
	PLASTIC FLUOROLOY G
	PLASTIC FLUOROLOY X
	PLASTIC FLUOROLOY Y
	PLASTIC FLUOROLOY Z
	PLASTIC FLUOROTEMP 103
	PLASTIC KEL-F CTFE CRYSTLLINE
	PLASTIC VICTREX PEEK 25% GLASS-FILLED
	RING 60% BRONZE FILLED TFE
	RUBBER SILICONE FMS510
	TAPE TFE/SILICONE 503-5-DC ADHESIVE
	TEFLON 55L2 SEALS
	TEFLON FEP
	TEFLON PTFE DISCS
	TEFLON TFE VIRGIN
	TEFLON TFE/25% GLASS
	TEFLON TFE/30% GLASS
	TEFZEL ETFE
	WIRE ELEC FEP WITH POLYIMIDE TAPE
FMC CORP	PLASTIC KRONITEX 100
	PLASTIC KRONITEX 1000
	PLASTIC KRONITEX 50
	PLASTIC KRONITEX CDD
	PLASTIC KRONITEX TCP
	PLASTIC KRONITEX TXP
FOAM CRAFT INC	INSULATION FOAM POLYURETHANE 50150
FOAM SYSTEMS	INSULATION FOAM POLYISOCYANURATE FSC18A
	INSULATION FOAM POLYISOCYANURATE FSC55
	INSULATION FOAM POLYISOCYANURATE FSC85A11
	INSULATION FOAM POLYURETHANE FSC55
FOAM SYSTEMS	INSULATION FOAM POLYURETHANE FSC83A-55
FOAMEX POLY PROD	INSULATION FOAM POLYURETHANE
FOMO PRODUCTS	INSULATION FOMO FILL
	SEALANT FOMOFIX POLYURETHANE
FOOTE MINERAL CO	ABSORBER CO2 LITHIUM HYDROXIDE
FORMULATED RESINS	ADHESIVE AF1120
	ADHESIVE AR1004
	ADHESIVE AR1005
	ADHESIVE AR1009
	ADHESIVE AR1100
	ADHESIVE AR1130
	ADHESIVE AR1150
	ADHESIVE AR1218
	ADHESIVE AR1418
	ADHESIVE AR1650
	ADHESIVE AR1700
	ADHESIVE AR1776
	ADHESIVE AR1930FR
	ADHESIVE CR3125
	ADHESIVE ECR4100
	ADHESIVE ECR4200
	ADHESIVE ECR4300
	ADHESIVE ECR4700
	ADHESIVE POLYTECH 4000
	ADHESIVE POLYTECH 4020
	ADHESIVE POLYTECH 4140
	ADHESIVE POLYTECH 4150
	ADHESIVE TCR12-100
	ADHESIVE TCR12-15
	ADHESIVE TCR2773
	ADHESIVE TCR2820
	PLASTIC ER2020
	PLASTIC ER2023
	PLASTIC ER2027
	PLASTIC ER2028
	PLASTIC ER2036
	PLASTIC ER2047
	PLASTIC ER2205
	PLASTIC ER2220
	PLASTIC ER2300
	PLASTIC ER2380
	PLASTIC ER2381
	PLASTIC ER2400
	PLASTIC ER3042
FORTIN CORP	FABRIC GLASS/EPOXY L1040-108
	LAMIN EPOXY/GLASS B10-108-63
	LAMIN EPOXY/GLASS TYPE GF
	LAMIN FORTIN CORE 1111
	LAMIN FORTIN CORE 2121
	LAMIN FORTIN CORE 2222
FOSTER GRANT	INSULATION FOAM STYRENE 4486
	INSULATION FOAM STYRENE 5486
FOSTER MILLER	TAPE MOLDED HOOK ULTENE PLASTIC EX1
FRALOCK	FILM P188-5/1 KAPTON/ACRYLIC
	LABEL IDENTIFICATION PAPER DOTS GREEN

MSFC-HDBK-527 REV F 9999942 0006900 9

Information Handling Services, 2000

NON-METALS DESIGNATIONS BY MANUFACTURER

MANUFACTURER	DESIGNATION
FRALOCK	TAPE POLYIMIDE PS
	TAPE POLYIMIDE T966
	TAPE TEFLON/ACRYLIC 3596 PS
FRANK MURKEN INC	RUBBER EPDM NOC
FRANKLIN INTERNATIONAL	ADHESIVE AB
	ADHESIVE AS
	ADHESIVE ASSEMBLY GLUE 160
	ADHESIVE ASSEMBLY GLUE 65
	ADHESIVE ASSEMBLY GLUE 70A
	ADHESIVE ASSEMBLY GLUE 8
	ADHESIVE ASSEMBLY GLUE 8 PLUS 5%
	ADHESIVE ASSEMBLY GLUE HIGH TACK
	ADHESIVE ASSEMBLY GLUE T2A
	ADHESIVE ASSEMBLY GLUE TX BROWN
	ADHESIVE LAMINATING 25
	ADHESIVE LAMINATING GLUE 6W
	ADHESIVE MULTIBOND AP1 WITH CAT A
	ADHESIVE MULTIBOND B
	ADHESIVE MULTIBOND C
	ADHESIVE MULTIBOND F
	ADHESIVE MULTIBOND LT1
	ADHESIVE MULTIBOND LT1 WITH CATALYST W
	ADHESIVE MULTIBOND RX
	ADHESIVE MULTIBOND W WITH CATALYST A
	ADHESIVE MULTIBOND W WITH CATALYST W
	ADHESIVE TITEBOND 35
	ADHESIVE TITEBOND 50
	ADHESIVE TITEBOND 55T
	ADHESIVE TITEBOND DOWEL DRIVER
	ADHESIVE TITEBOND IMPERIAL
	ADHESIVE TITEBOND REGULAR
	ADHESIVE TITEBOND SUPREME
	ADHESIVE TOPSPEED ASSEMBLY GLUE
	ADHESIVE WILLBOND 10
	ADHESIVE WOODBOND 285
FREEMAN CHEMICAL CORP	COATING 515X346 EPOXY
	PLASTIC 46-8012
	PLASTIC ACPOL 42-2640
	PLASTIC ACPOL 42-2673
	PLASTIC ACPOL 42-2675
	PLASTIC FREEFLO 49-0301
	PLASTIC INTERPOL 047-1050
	PLASTIC NUPOL 46-4001
	PLASTIC NUPOL 46-4003
	PLASTIC NUPOL 46-4004
	PLASTIC NUPOL 46-4008
	PLASTIC NUPOL 46-4013
	PLASTIC NUPOL 46-4020
	PLASTIC NUPOL 46-4076
	PLASTIC NUPOL 46-4250
	PLASTIC NUPOL 46-4400
	PLASTIC NUPOL 46-4421
	PLASTIC NUPOL 46-4435
	PLASTIC NUPOL 46-4440
	PLASTIC NUPOL 46-8000
FREEMAN CHEMICAL CORP	PLASTIC NUPOL 46-8016
	PLASTIC STYPOL 047-1000
	PLASTIC STYPOL 047-1050
	PLASTIC STYPOL 40-0008
	PLASTIC STYPOL 40-0042
	PLASTIC STYPOL 40-0048
	PLASTIC STYPOL 40-0087
	PLASTIC STYPOL 40-1021
	PLASTIC STYPOL 40-1037
	PLASTIC STYPOL 40-1103
	PLASTIC STYPOL 40-1117
	PLASTIC STYPOL 40-1124
	PLASTIC STYPOL 40-1507
	PLASTIC STYPOL 40-1602
	PLASTIC STYPOL 40-1603
	PLASTIC STYPOL 40-2025
	PLASTIC STYPOL 40-2026
	PLASTIC STYPOL 40-2057
	PLASTIC STYPOL 40-2072
	PLASTIC STYPOL 40-2092
	PLASTIC STYPOL 40-2304
	PLASTIC STYPOL 40-2353
	PLASTIC STYPOL 40-2364
	PLASTIC STYPOL 40-2405
	PLASTIC STYPOL 40-2448
	PLASTIC STYPOL 40-2465
	PLASTIC STYPOL 40-2580
	PLASTIC STYPOL 40-2584
	PLASTIC STYPOL 40-2780
	PLASTIC STYPOL 40-2782
	PLASTIC STYPOL 40-27II
	PLASTIC STYPOL 40-2974
	PLASTIC STYPOL 40-2988
	PLASTIC STYPOL 40-2989
	PLASTIC STYPOL 40-2990
	PLASTIC STYPOL 40-3267
	PLASTIC STYPOL 40-3303
	PLASTIC STYPOL 40-3323
	PLASTIC STYPOL 40-3904
	PLASTIC STYPOL 40-3906
	PLASTIC STYPOL 40-3909
	PLASTIC STYPOL 40-3925
	PLASTIC STYPOL 40-3925 43% GLASS
	PLASTIC STYPOL 40-3925 50% GLASS
	PLASTIC STYPOL 40-3929
	PLASTIC STYPOL 40-3939
	PLASTIC STYPOL 40-3941
	PLASTIC STYPOL 40-3950
	PLASTIC STYPOL 40-4901
	PLASTIC STYPOL 40-4902
	PLASTIC STYPOL 40-4920
	PLASTIC STYPOL 40-5013
	PLASTIC STYPOL 40-6519
	PLASTIC STYPOL 40-7001
	PLASTIC STYPOL 40-7052

MSFC-HDBK-527 REV F 9999942 0006901 0

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
FREEMAN CHEMICAL CORP	PLASTIC STYPOL 40-7114
	PLASTIC STYPOL 40-7116
	PLASTIC STYPOL 40-7119
	PLASTIC STYPOL 40-7131
	PLASTIC STYPOL 40-7134
	PLASTIC STYPOL 40-7193
	PLASTIC STYPOL 40-7263
	PLASTIC STYPOL 40-8003
	PLASTIC STYPOL 40-8408
	PLASTIC STYPOL 40-9303
	PLASTIC STYPOL 40-9311
	PLASTIC STYPOL 40-9518
	PLASTIC STYPOL 40-I029
	PLASTIC STYPOL 42-2640
	PLASTIC STYPOL 42-2675
	PLASTIC STYPOL 70-0001
	PLASTIC STYPOL 70-0004
	PLASTIC STYPOL 72-5038
	PLASTIC STYPOL 80-1126
	PLASTIC STYPOL 80-3297
	PLASTIC STYPOL 80-II20
	PLASTIC STYPOL 80-II27
	PLASTIC STYPOL 83-2000
	PLASTIC STYPOL 83-2030
	PLASTIC STYPOL 83-2035
	PLASTIC STYPOL 83-2105
	PLASTIC STYPOL 83-2139
	PLASTIC STYPOL 83-2140
FUHRMAN DIVERSIFIED	FLASHLIGHT STREAMLITE 15
FUJI RUBBER	CONNECTOR ELASTOMERIC ZEBRA STRIPS FSC-C-.002 PITCH
FUJIKURA KASEI	RUBBER SILICONE 1671
FULLER O'BRIEN CORP	COATING 421-03 GRAY
	COATING EPOXY/POLYAMIDE WHITE
FULTON FABRICS	GLOVE COMFORT NYLON/TRICOT
FURANE	ADHESIVE 2223 A/B EPOXY
	ADHESIVE EPIBOND 104 A/B
	ADHESIVE EPIBOND 115 EPOXY
	ADHESIVE EPIBOND 1210A/9610
	ADHESIVE EPIBOND 1210A/9615-10
	ADHESIVE EPIBOND 1210A/9615-62
	ADHESIVE EPIBOND 1210A/9861
	ADHESIVE EPIBOND 1217 A/B
	ADHESIVE EPIBOND 1218 A/B
	ADHESIVE EPIBOND 123/931 EPOXY
	ADHESIVE EPIBOND 126 A/B
	ADHESIVE EPIBOND 1337
	ADHESIVE EPIBOND 1337/9514A
	ADHESIVE EPIBOND 1337/9615A
	ADHESIVE EPIBOND 1526
	ADHESIVE EPIBOND 153 A/B
	ADHESIVE EPIBOND 1534 A/B
	ADHESIVE EPIBOND 1537
	ADHESIVE EPIBOND 1539
	ADHESIVE EPIBOND 1543 A/B

MANUFACTURER	DESIGNATION
FURANE	ADHESIVE EPIBOND 1544
	ADHESIVE EPIBOND 1545
	ADHESIVE EPIBOND 1546
	ADHESIVE EPIBOND 1547
	ADHESIVE EPIBOND 1548
	ADHESIVE EPIBOND 156 A/B
	ADHESIVE EPIBOND 156/956
	ADHESIVE EPIBOND 7000 A/B
	ADHESIVE EPIBOND 7001 A/B
	ADHESIVE EPIBOND 7002
	ADHESIVE EPIBOND 7004
	ADHESIVE EPIBOND 7100 A/B
	ADHESIVE EPIBOND 7102
	ADHESIVE EPIBOND 7103
	ADHESIVE EPIBOND 7200
	ADHESIVE EPIBOND 7202
	ADHESIVE EPIBOND 7300
	ADHESIVE EPIBOND 7301
	ADHESIVE EPIBOND 7375
	ADHESIVE EPIBOND 8287 EPOXY
	ADHESIVE EPIBOND 8543 A/B
	ADHESIVE EPIBOND 87399 EPOXY
	ADHESIVE EPIBOND 87680
	ADHESIVE EPIBOND 87803
	ADHESIVE EPIBOND 88434
	ADHESIVE EPIBOND 88807
	ADHESIVE EPIBOND X87336 EP/AG FIL
	ADHESIVE EPOCAST 1310 MOD-I/9223
	ADHESIVE EPOCAST 212 EPOXY
	ADHESIVE EPOCAST 2201/C951
	ADHESIVE EPOCAST 290 EPOXY
	ADHESIVE EPOCAST 290 T2
	ADHESIVE EPOCAST 290/9810
	ADHESIVE EPOCAST 35
	ADHESIVE EPOCAST 45
	ADHESIVE EPOCAST 50-1
	ADHESIVE EPOCAST 50-2
	ADHESIVE EPOCAST 50-3
	ADHESIVE EPOCAST 8542/38/9242 EPX
	ADHESIVE EPOCAST 87005 A/B-60
	ADHESIVE EPOCAST 88757
	ADHESIVE EPON 828/EPOCAST HN951
	ADHESIVE URALANE 5738 A/B POLYURETHANE
	ADHESIVE URALANE 5753 POLYURETHANE
	ADHESIVE URALANE 5754 A/B
	ADHESIVE URALANE 5759 A/B
	ADHESIVE URALANE 5764 A/B
	ADHESIVE URALANE 5767
	ADHESIVE URALANE 5768
	ADHESIVE URALANE 8089
	ADHESIVE URALANE 8267 POLYURETHANE
	ADHESIVE URALANE 88800
	ADHESIVE URALANE 88804
	COATING URALANE 5750 A/B
	COMPOUND URALANE/GLASS 12887-547

MSFC-HDBK-527 REV F 9999942 0006902 2

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
FURANE	COMPOUND URALANE/GLASS 12887-556
	COMPOUND URALANE/GLASS 5753LV A1
	COMPOUND URALANE/GLASS 5753LV B1
	COMPOUND URALANE/GLASS 5753LV C1
	COMPOUND URALANE/GLASS 5753LV V1
	COMPOUND URALANE/GLASS 5753LV X1
	COMPOUND URALANE/GLASS 5753LV Z1
	LAMIN EPOCAST 31/9216/1581 CLOTH
	LAMIN EPOXY/GLASS FURANE 203
	MOLD COMPOUND EPOCAST 409-608 EPOXY
	PLASTIC EPOCAST 11B/9812
	PLASTIC EPOCAST 31B/9216
	PLASTIC EPOCAST 31D/9216
	PLASTIC EPOCAST 31D/927
	PLASTIC EPOCAST 32 A/B
	PLASTIC EPOCAST 417
	PLASTIC EPOCAST 420
	PLASTIC EPOCAST 432
	PLASTIC EPOCAST 442
	PLASTIC EPOCAST 443
	PLASTIC EPOCAST 452
	PLASTIC EPOCAST 460
	PLASTIC EPOCAST 461
	PLASTIC EPOCAST 471
	PLASTIC EPOCAST 475
	PLASTIC EPOCAST 4B A/9816
	PLASTIC EPOCAST 4D A/951
	PLASTIC EPOCAST 4D A/9633
	PLASTIC EPOCAST 50 A/9449
	PLASTIC EPOCAST 50 A/946
	PLASTIC EPOCAST 50 A/9816
	PLASTIC EPOCAST 9 A/B
	PRINTED WIRING BOARD COPPER CLAD/POLYIMIDE
	GLASS/CAT-L-INK 50-100 MARKING 1 TO 3 MIL
	S THICK/URALANE 5075 CONFORMAL COATING 3
	TO 5 MILS THICK
	RUBBER URALANE 1440 A/B
	RUBBER URALANE 1460 A/B
	RUBBER URALANE 87645 A/B
	RUBBER URALANE 87647 A/B
FUSECOTE CO	COATING FUSECOTE 879 WITH 1000 EPOXY
	COATING FUSECOTE REP35212-50
	COATING FUSECOTE VE211-7A EPOXY
FUSION INC	PASTE SILVER SOLDER
FUTURA COATING INC	COATING 550/5007/FOAM 658 POLYURETHANE
	COATING URETHANE 550/5007 BASE
FWF IND INC	YARN STYLE 7511
G & D INDUSTRIES	LAMIN GLASS CLOTH
	RUBBER SILICONE RTV 7500-511/FIBERGLASS
G S F PLASTICS	GASKET RING FC-171
	GASKET RING FC-192
	GASKET RING FC-195
	GASKET RING GSF-1100
GACO WESTERN INC	COATING HYPALON 150W-8
	COATING HYPALON HFR2200 WHITE
GACO WESTERN INC	COATING HYPALON/GACOFLEX H2200 WHITE
	COATING HYPALON/GACOFLEX HFR2200
	COATING RUBBER HYPALON NOC
	CORK/HYPALON HFR2200
	CORK/HYPALON HFR2200/ACTIVATOR
	INSULATION FOAM CPR920-9-2/HFR2200 PS
	INSULATION FOAM POUR P2801
	POLYISOCYANURATE
	MSA FOAM COATED WITH HYPALON HFR2200
	MSA/HYPALON HFR2200/ACTIVATOR
GAF CORP	FELT NOMEX 61HT/14
GALTEK CORP	TUBING TEFLON 350 DISPOSAL
GARLOCK	FLUOROGRAY 5330-084-1774
	FLUOROGRAY 5330-LNO-2628X
	FLUOROGRAY 5330-LNO-2638X
	TEFLON PTFE MULTIFILL 427
GATES ENGINEERING CO INC	ADHESIVE G10
	ADHESIVE GACO AL45
	ADHESIVE GACO CE2
	ADHESIVE HP12
	ADHESIVE N6H
	ADHESIVE N7
GATES MFG CO	BELT POLYFLEX 8C84C077 COTTON/POLYESTER
	HOSE NEOPRENE TYPE A
GDSS	MULTI-LAYERED INSULATION RADIATION SHIELD
GELMAN SCIENCES INC	FILTER MATERIAL VERSAPOR 10000
GEMINI PLASTICS	FILM WRIGHTLON 7400
GENERAL DESIGN INC	TUBING FIBERGLASS/SILICONE 3298-1
GENERAL DISPERSION	SEALANT FRAYCHECK
GENERAL DYNAMICS	LAMIN CORLAR 4102/KEVLAR 49-181
	LAMIN CORLAR 5105/KEVLAR 49-181
	LAMIN CORLAR 5134/KEVLAR 49-181
	LAMIN CORLAR 6101-2/KEVLAR 49-18
	LAMIN EPOXY/GRAPHITE GY70/X30
	LAMIN EPOXY/KEVLAR F164/KEVLAR 49
	LAMIN KERIMID 601/KEVLAR 49-181
	LAMIN KEVLAR 49-181/SKYBOND 703
	LAMIN KEVLAR 49/SKYBOND 703
	LAMIN PYRALIN 3001/KEVLAR 49-181
	LAMIN PYRALIN 3003/KEVLAR 49-181
	LUBE OIL WD40/LEEDER 241K
	LUBE OIL WD40/M6 SEE REPORT
	MULTI-LAYERED INSULATION RADIATION SHIELD
	TEFLON
	POTTING COMPOUND EPOXY 0-73027-1
GENERAL ELECTRIC	ABLATIVE COMPOUND EPOXY PD451A
	ADHESIVE G623
	ADHESIVE G624
	ADHESIVE G627
	ADHESIVE G635
	ADHESIVE G641
	ADHESIVE G662
	ADHESIVE G687
	ADHESIVE G697
	ADHESIVE GLYPTAL 7526F

MSFC-HDBK-527 REV F 9999942 0006903 4

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
GENERAL ELECTRIC	ADHESIVE IS802
	ADHESIVE IS803
	ADHESIVE IS808
	ADHESIVE MPC52 A/B EPOXY
	ADHESIVE N-SIL RTV 122
	ADHESIVE N-SIL RTV 123
	ADHESIVE N-SIL RTV 128
	ADHESIVE RTV 109
	ADHESIVE RTV 161
	ADHESIVE RTV 31
	ADHESIVE RTV 41
	ADHESIVE RUBBER SILICONE RTV 1473
	ADHESIVE RUBBER SILICONE RTV 157
	ADHESIVE RUBBER SILICONE RTV 158
	ADHESIVE SE851/CA2
	ADHESIVE SE871/CA2
	ADHESIVE SE881/CA2
	ADHESIVE SILGRIP PSA6573
	ADHESIVE SILGRIP SR529 SILICONE
	ADHESIVE SILGRIP SR573 SILICONE
	ADHESIVE SILGRIP SR6573 SILICONE
	ADHESIVE SILGRIP SR6574 SILICONE
	ADHESIVE SILICONE BLK GL FIL
	ADHESIVE SR529/SRC18
	BAG CONTINGENCY P/N 47A232804
	COATING D4D THERMAL CONTROL ALUMINUM/ SILICONE
	COATING GLYPTAL 1201 RED
	COATING INK/ADHESIVE ON LEXAN
	COATING PRIMER SS4120
	COATING RTV 11/T12 SILICONE
	COATING SHC1200 HARDCOAT
	COATING SILICONE SEA200G ADHES
	COATING SILICONE SR80 RESIN
	COATING SS4004 SS4004 SILANE
	COATING SS4155 SILANE
	COATING VARNISH GLPT RED
	COMPOUND HEAT SINK SILICONE VB
	COMPOUND HEAT TRANSFER G642 SILICONE
	COMPOUND THERMAL CONDUCTIVE URETHANE SMRD 902
	CONTAINER FOOD NYLON
	FABRIC GLASS/SILICONE
	FABRIC NOMEX BLUE FLIGHT SUIT
	HOSE FLEX RTV 630
	INSULATION BLANKET KAPTON/MYLAR/DACRON
	INSULATION FOAM NORYL FN215
	INSULATION FOAM POLYCARBONATE 141/FLC95/ BLK701
	INSULATION FOAM POLYETHER URETHANE RIGID
	INSULATION FOAM POLYURETHANE
	INSULATION FOAM SILICONE RTF762/SF9650
	INSULATION FOAM THERMOTROL 2122 POLYURETHANE
	INSULATION SMRD 100F90
GENERAL ELECTRIC	INSULATION SMRD 100F90/FR 13
	INSULATION SMRD 100F90/FR 7
	LACING TAPE POLYESTER
	LAMIN EPOXY/GLASS G10FR/SR240
	LAMIN EPOXY/GLASS VIBRATION DAMPER
	LAMIN EPOXY/GLASS WITH EPOXYLITE 9653
	LAMIN LEXAN/TEDLAR
	LAMIN PHENOLIC/NYLON
	LAMIN PHENOLIC/PAPER
	LAMIN POLYETHYLENE/SARANEX 23
	LAMIN TEXTOLITE 11508
	LAMIN TEXTOLITE 11546
	LUBE GREASE SILICONE G683
	LUBE GREASE SILICONE GE688
	LUBE GREASE VERSILUBE G300
	LUBE OIL VERSILUBE F50 SILICONE
	LUBE OIL VISCASIL 10000 SILICONE
	MOLD COMPOUND NORYL EN-265
	MOLD COMPOUND NORYL SE-1
	MOLD COMPOUND NORYL SE-1-GFN3 30
	MOTOR ELECTRIC P/N 47A232920A
	MULTI-LAYERED INSULATION KAPTON/MYLAR/ DACRON NET
	PACKAGE FOOD SARAN/POLYETHYLEN
	PANEL LEXAN 934111 EDGELIGHTED
	PAPER JCP K-10
	PCB CONNECTOR/VALOX 420/RYTON
	PLASTIC LEXAN 101
	PLASTIC LEXAN 103
	PLASTIC LEXAN 104
	PLASTIC LEXAN 121
	PLASTIC LEXAN 123
	PLASTIC LEXAN 124
	PLASTIC LEXAN 141
	PLASTIC LEXAN 141 POLYCARBONATE
	PLASTIC LEXAN 141L
	PLASTIC LEXAN 144
	PLASTIC LEXAN 1500
	PLASTIC LEXAN 151
	PLASTIC LEXAN 153
	PLASTIC LEXAN 154
	PLASTIC LEXAN 161
	PLASTIC LEXAN 181
	PLASTIC LEXAN 191
	PLASTIC LEXAN 193
	PLASTIC LEXAN 303
	PLASTIC LEXAN 3412 20% GLASS
	PLASTIC LEXAN 3413 30% GLASS
	PLASTIC LEXAN 3414 40% GLASS
	PLASTIC LEXAN 500 10% GLASS
	PLASTIC LEXAN 503
	PLASTIC LEXAN 9030 POLYCARBONATE
	PLASTIC LEXAN 9034 NATURAL POLYCARBONATE
	PLASTIC LEXAN 9034-112

MSFC-HDBK-527 REV F 9999942 0006904 6

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
GENERAL ELECTRIC	PLASTIC LEXAN 9034-112/A4T COATING OVER DC Q9-6312
	PLASTIC LEXAN 920
	PLASTIC LEXAN 920A
	PLASTIC LEXAN 940 POLYCARBONATE
	PLASTIC LEXAN 940A
	PLASTIC LEXAN 9410 WHITE POLYCARBONATE
	PLASTIC LEXAN 950
	PLASTIC LEXAN 950A
	PLASTIC LEXAN 9600 FR NATURAL
	PLASTIC LEXAN 9600 NATURAL POLYCARBONATE
	PLASTIC LEXAN 9600 NATURAL POLYCARBONATE TOX RATE STUDY
	PLASTIC LEXAN 9600-116 POLYCARBONATE
	PLASTIC LEXAN 9604 FR NATURAL POLYCARBONATE
	PLASTIC LEXAN 9604-71063 POLYCARBONATE
	PLASTIC LEXAN BE1
	PLASTIC LEXAN F2000 POLYCARBONATE
	PLASTIC LEXAN F6000 POLYCARBONATE
	PLASTIC LEXAN F60061 POLYCARBONATE
	PLASTIC LEXAN FL900
	PLASTIC LEXAN GF3000 POLYCARBONATE
	PLASTIC LEXAN HF1110
	PLASTIC LEXAN HF1130
	PLASTIC LEXAN HF2110
	PLASTIC LEXAN HF2130
	PLASTIC LEXAN HP1
	PLASTIC LEXAN HP2
	PLASTIC LEXAN HP3
	PLASTIC LEXAN HP4
	PLASTIC LEXAN HP5
	PLASTIC LEXAN MARGARD MR5004-112
	PLASTIC LEXAN MR4000 SERIES
	PLASTIC LEXAN OQ1
	PLASTIC LEXAN POLYCARBONATE CLEAR
	PLASTIC LEXAN PPC4501
	PLASTIC LEXAN PPC4701
	PLASTIC LEXAN SG403-82311
	PLASTIC LEXAN SL29
	PLASTIC LEXAN WR2210
	PLASTIC LOMOD B0100
	PLASTIC LOMOD B0150
	PLASTIC LOMOD B0200
	PLASTIC LOMOD B0220
	PLASTIC LOMOD B0250
	PLASTIC LOMOD B0800
	PLASTIC LOMOD B0852
	PLASTIC LOMOD R0520
	PLASTIC NORYL 1222
	PLASTIC NORYL 1390
	PLASTIC NORYL 1391
	PLASTIC NORYL 722
	PLASTIC NORYL 731
	PLASTIC NORYL 844

MANUFACTURER	DESIGNATION
GENERAL ELECTRIC	PLASTIC NORYL 888
	PLASTIC NORYL CRT200
	PLASTIC NORYL EN185
	PLASTIC NORYL EN212
	PLASTIC NORYL GFN2
	PLASTIC NORYL GFN3
	PLASTIC NORYL GTX 810
	PLASTIC NORYL GTX 820
	PLASTIC NORYL GTX 830
	PLASTIC NORYL GTX 910
	PLASTIC NORYL HB235
	PLASTIC NORYL HS1000
	PLASTIC NORYL HS2000
	PLASTIC NORYL N190
	PLASTIC NORYL N225
	PLASTIC NORYL N300
	PLASTIC NORYL PC180
	PLASTIC NORYL PLUS CRN410
	PLASTIC NORYL PLUS CRN639
	PLASTIC NORYL PLUS RNF420
	PLASTIC NORYL PLUS RNF430
	PLASTIC NORYL PLUS SPN410
	PLASTIC NORYL PLUS SPN420
	PLASTIC NORYL PLUS SPN422L
	PLASTIC NORYL PLUS SPN580
	PLASTIC NORYL PLUS SPN585H
	PLASTIC NORYL PLUS UVN580
	PLASTIC NORYL PN235
	PLASTIC NORYL PX0722
	PLASTIC NORYL PX1222
	PLASTIC NORYL PX1265
	PLASTIC NORYL PX1390
	PLASTIC NORYL PX1391
	PLASTIC NORYL PX844
	PLASTIC NORYL PX888
	PLASTIC NORYL SE 100
	PLASTIC NORYL SE1-CFN2
	PLASTIC NORYL SE1/GFN2
	PLASTIC NORYL SE1/GFN3
	PLASTIC NORYL UV180
	PLASTIC ULTEM 1000
	PLASTIC ULTEM 1010
	PLASTIC ULTEM 2400
	PLASTIC ULTEM 4000
	PLASTIC ULTEM 4001
	PLASTIC ULTEM 6000
	PLASTIC ULTEM 6100
	PLASTIC ULTEM 6200
	PLASTIC ULTEM 6202
	PLASTIC VALOX 325
	PLASTIC VALOX 357
	PLASTIC VALOX 365
	PLASTIC VALOX 414 40% GLASS
	PLASTIC VALOX 420 30% GLASS
	PLASTIC VALOX 420 SEO POLYESTER/GLASS

MSFC-HDBK-527 REV F 9999942 0006905 8

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
GENERAL ELECTRIC	PLASTIC VALOX 430 30% GLASS
	PLASTIC VALOX 508 30% GLASS
	PLASTIC VALOX 553 30% GLASS
	PLASTIC VALOX 701 35% GLASS
	PLASTIC VALOX 730
	PLASTIC VALOX 730-1001 POLYESTER
	PLASTIC VALOX 735 40% GLASS
	PLASTIC VALOX 736
	PLASTIC VALOX 740 30% MINERAL
	PLASTIC VALOX 752 45% GLASS
	PLASTIC VALOX 760 25% MINERAL
	PLASTIC VALOX 780 40% GLASS
	PLASTIC VALOX 815 15% GLASS
	PLASTIC VALOX 830 30% GLASS
	PLASTIC VALOX 850 15% GLASS
	PLASTIC VALOX 855 15% GLASS
	PLASTIC VALOX 865 30% GLASS
	PLASTIC VALOX DR-48 15% GLASS
	PLASTIC VALOX DR-51 15% GLASS
	PLASTIC XENOY 2230
	PLASTIC XENOY 3220
	PLASTIC XENOY 3221
	PLASTIC XENOY 3225
	PLASTIC XENOY 5220
	PLASTIC XENOY 6120
	PLASTIC XENOY 6121
	PLASTIC XENOY 6123
	PLASTIC XENOY 6240 10% GLASS
	PLASTIC XENOY 6370 30% GLASS
	PLASTIC XENOY 6380 30% GLASS
	PLASTIC XENOY 6620
	POTTING COMPOUND RTV 11/C12
	POTTING COMPOUND RTV 11/C9811
	ROD REINFORCED GRAPHITE/PHENOLIC
	RUBBER PHENYL
	RUBBER RTV 12C
	RUBBER RTV 12W
	RUBBER RTV 511
	RUBBER RTV 577/T-12/SS4415/A276
	RUBBER RTV 6157
	RUBBER RTV 627
	RUBBER RTV 660
	RUBBER RTV 662
	RUBBER RTV 668
	RUBBER RTV 670
	RUBBER RTV 700 BETA 1
	RUBBER RTV 700 BETA 2
	RUBBER RTV 700 BETA 4
	RUBBER RTV 700 BETA 5
	RUBBER RTV 8262
	RUBBER SE5559U
	RUBBER SILASTIC RTV 732
	RUBBER SILICONE 1000PSI HARDNESS 45 - 55
	RUBBER SILICONE 159
	RUBBER SILICONE 4524

MANUFACTURER	DESIGNATION
GENERAL ELECTRIC	RUBBER SILICONE 555
	RUBBER SILICONE 566/NAPTHA SOLV
	RUBBER SILICONE CV2500
	RUBBER SILICONE O-RINGS
	RUBBER SILICONE RA-5211U
	RUBBER SILICONE RTV 102
	RUBBER SILICONE RTV 103
	RUBBER SILICONE RTV 106
	RUBBER SILICONE RTV 108
	RUBBER SILICONE RTV 112
	RUBBER SILICONE RTV 116
	RUBBER SILICONE RTV 118
	RUBBER SILICONE RTV 12 A/B
	RUBBER SILICONE RTV 133
	RUBBER SILICONE RTV 142
	RUBBER SILICONE RTV 156
	RUBBER SILICONE RTV 162
	RUBBER SILICONE RTV 168
	RUBBER SILICONE RTV 21
	RUBBER SILICONE RTV 281-400S
	RUBBER SILICONE RTV 511/SS4155
	RUBBER SILICONE RTV 560
	RUBBER SILICONE RTV 560 TOX RATE STUDY
	RUBBER SILICONE RTV 560/577
	RUBBER SILICONE RTV 560/9811
	RUBBER SILICONE RTV 566
	RUBBER SILICONE RTV 577
	RUBBER SILICONE RTV 577 TOX RATE STUDY
	RUBBER SILICONE RTV 577/9811
	RUBBER SILICONE RTV 577/T12
	RUBBER SILICONE RTV 60
	RUBBER SILICONE RTV 602 CLEAR
	RUBBER SILICONE RTV 615
	RUBBER SILICONE RTV 616
	RUBBER SILICONE RTV 630
	RUBBER SILICONE RTV 630/50% OIL
	RUBBER SILICONE RTV 632
	RUBBER SILICONE RTV 634
	RUBBER SILICONE RTV 652
	RUBBER SILICONE RTV 655
	RUBBER SILICONE RTV 700
	RUBBER SILICONE RTV 8111/C989
	RUBBER SILICONE RTV 8112 C9858
	RUBBER SILICONE RTV 90
	RUBBER SILICONE RTV DC3-6077
	RUBBER SILICONE SE4404
	RUBBER SILICONE SE5211
	RUBBER SILICONE SE5403
	RUBBER SILICONE SE5549
	RUBBER SILICONE SE5559
	RUBBER SILICONE SE5601
	RUBBER SILICONE SE565
	RUBBER SILICONE SE7600
	SPONGE RUBBER SILICONE F760
	SPONGE RUBBER SILICONE PD200-16

MSFC-HDBK-527 REV F 9999942 0006906 T

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
GENERAL ELECTRIC	SPONGE RUBBER SILICONE PD200-16 SILICONE
	SPONGE RUBBER SILICONE PD200-16/RTV560
	SPONGE RUBBER SILICONE PD200-16/RTV560/ PD147
	SPONGE RUBBER SILICONE RT 762 FR
	TAPE POLYESTER/GLASS 76593
	VARNISH GLYPTAL 1202 ALK
	VARNISH SR80 SILICONE
	WIRE ELEC KAPTON TAPE/GLASS TUBE
	WIRE ELEC RAYCHEM 44 MYLAR/KAPTON
	WIRE ELEC RAYCHEM 44/KAPTON
	WIRE ELEC RAYCHEM CU/MYLAR/KAPTON
	WIRE ELEC WITH FIBERGLASS SLEEVE
	WIRE ELEC WITH METAL BRAID SHIELD
GENERAL FOAM CORP	INSULATION FOAM DENSITE 4 GUARDIAN/G 8003
GENERAL LATEX	BLADDER NEOPRENE 3N868 NO4/6
	INSULATION FOAM POLYISOCYANURATE XR1002
GENERAL MAGNAPLATE	COATING NEDOX SF2 TEFLON
	COATING TEFLON INFUSED
	LUBE DRY NEDOX U4 FILM
GENERAL MILLS	ADHESIVE EPON 828/VERSAMID 125
	ADHESIVE VERSALON XR1200 POLYAMIDE
GENERAL PLASTICS	FOAM POLYURETHANE LAST-A-FOAM
	INSULATION FOAM LAST-A-FOAM POLYURETHANE FR3704
	INSULATION FOAM LAST-A-FOAM POLYURETHANE FR6709
	INSULATION FOAM POLYURETHANE FR6704/EC2241 4PCF
	MULTI-LAYERED INSULATION POLYURETHANE FOAM 416/SUPER KOROPON/RTV 560/HYPALON
	TUBING GENCOTE 125C
GENTEX CORP	EARSEAL 61B883 URETHANE/FLOURL
	LAMIN VANOXY 128/VERSAMID 140F
	RUBBER NEOPRENE/HELMET LINER
GEORGE C MOORE CO	FABRIC ELASTIC 1700 1.0 WIDE
	WEBBING ELASTIC 1707
	WEBBING POLYESTER 562 PLASTIC
GEORGE HARRIS CORP	FABRIC DACRON S1185
GERING PLASTICS	FILM PERFLEX-E POLYURETHANE
GFE	FILM POLYETHYLENE8135-00-006-5962
	INK LUMOCOLOR 317
	INK PEN 60 SILVER
	INK PRINTERS BLACK D6668 ON #60 SCOTT PAPER
	PLASTIC YELLOW VINYL CAPS FORMULA 701
	RUBBER BAND NATURAL OR SYNTHETIC SIZE 64
	SHROUD CUTTER P/N60C6037
	TAPE CORRECT 7510-00-634-5110
GIBRALTER INDUSTRIES	FABRIC AROMATIC POLYAMIDE
GIBSON-HOMANS CO	ADHESIVE SHURSTIK 486
GILBERT INTERNATIONAL	TAPE DISSOLVO WELDING ADHESIVE
GILLETTE	BLADE RAZOR DOUBLE EDGED PLATE
	CREME SHAVE BRUSHLESS
	RAZOR GILLETTE TRAC II
GILLETTE	RAZOR SAFETY SUPER 84
GLADDING CORP	CORD NYLON
	CORD NYLON BRAIDED 50
	CORD POLYESTER 80
	LINE CASTING WHITE GHOST NYLON
GLASTIC	PLASTIC GLASROD HIR
	PLASTIC GLASROD MTS
	PLASTIC GLASROD SG200
	PLASTIC GLASTIC GPO3
GLEN RAVEN MILLS	FABRIC SUNBRELLA FIRESIST 8601 ARTIC BLUE
GLENAIR	ADAPTER CONNECTOR KYNAR/SS
	FEEDTHRU CONNECTOR KYNAR/SS
	MICROPHONE HANDHELD PLUG/CABLE
	TUBING KYNAR CONVOLUTED BLACK
GLIDDEN	ADHESIVE AP138 ALL IN ONE
	ADHESIVE AP139 ALL IN ONE
	ADHESIVE CB10
	ADHESIVE CT20
	ADHESIVE DW24
	ADHESIVE FS145
	ADHESIVE MACCO AW40
	ADHESIVE MACCO BL70
	ADHESIVE MACCO C5
	ADHESIVE MACCO CA80
	ADHESIVE MACCO CA90
	ADHESIVE MACCO CERAMIC WALL TILE ADHESIVE M111
	ADHESIVE MACCO LIQUID NAILS LN60
	ADHESIVE MACCO LIQUID NAILS LN601
	ADHESIVE MACCO LIQUID NAILS LN602
	ADHESIVE MACCO LIQUID NAILS LN603
	ADHESIVE MACCO LUQUID ROOF REPAIR LR808
	ADHESIVE MACCO LUQUID WEATHER STRIP LN165
	ADHESIVE MACCO M112
	ADHESIVE MACCO M220
	ADHESIVE MACCO M221
	ADHESIVE MACCO PV20
	ADHESIVE MACCO RC711
	ADHESIVE MACCO SB60
	ADHESIVE MACCO TA605
	ADHESIVE MACCO WG166
	ADHESIVE MACCO WOODWORKERS' GLUE
	SEALANT PUTTY 453 5 K36 BLK
GLOBAL CHEMICAL SYS	INSULATION POLYURETHANE SHEET 4050
	INSULATIOON POLYURETHANE SHEET 4070
GLOBE ALBANY CORP	FABRIC NOMEX S2352NBR FILTER
	FABRIC NOMEX/BETA GLASS 2458N
	FELT NOMEX S2335 NRB/Z
	FELT NOMEX STYLE 190R
	INSULATION FELT NOMEX TYPE E
	MOTOR GLOBE 43A1578
GOAL CHEMICAL SEALANTS CORP	ADHESIVE GC1100
	ADHESIVE GC131 ADHESIVE PRIMER
	ADHESIVE GC1500 CLASS A
	ADHESIVE GC1500 CLASS B

MSFC-HDBK-527 REV F 9999942 0006907 1

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
GOAL CHEMICAL SEALANTS CORP	ADHESIVE GC1900
	ADHESIVE GC200 CLASS A
	ADHESIVE GC200 CLASS B
	ADHESIVE GC3001
	ADHESIVE GC3007
	ADHESIVE GC401 CLASS A
	ADHESIVE GC401 CLASS B
	ADHESIVE GC401LD CLASS A
	ADHESIVE GC401LD CLASS B
	ADHESIVE GC402
	ADHESIVE GC407 CLASS A
	ADHESIVE GC407 CLASS B
	ADHESIVE GC408 CLASS A
	ADHESIVE GC408 CLASS B
	ADHESIVE GC409 CLASS B
	ADHESIVE GC414 CLASS B2
	ADHESIVE GC435
	ADHESIVE GC450 CLASS A
	ADHESIVE GC450 CLASS B
	ADHESIVE GC450 CLASS C
	ADHESIVE GC502
	ADHESIVE GC531 MYLAR ADHESIVE (AEROSPACE)
	ADHESIVE GC656 ADHESIVE GAP FILLING
	ADHESIVE GC825 FLEXIBLE EPOXY ADHESIVE
	ADHESIVE GC92
	ADHESIVE GCL455 CLASS B
	RUBBER GC202 CLASS B
GOLDEN STATE/LATEX	COATING NEOPRENE LN2500A
GOLDEN WEST PRODUCTS	INSULATION FOAM GOLDEN WEST 9-12
GOODLOE INC	ADHESIVE TUFFBOND
	ADHESIVE TUFFBOND QUIK SET
GOODYEAR	ACOUSTA STYLE 200
	ADHESIVE PLIOBOND
	ADHESIVE PLIOBOND 1000
	ADHESIVE PLIOBOND 1001
	ADHESIVE PLIOBOND 1005
	ADHESIVE PLIOBOND 1008
	ADHESIVE PLIOBOND 1012
	ADHESIVE PLIOBOND 1014-44
	ADHESIVE PLIOBOND 1016
	ADHESIVE PLIOBOND 1018
	ADHESIVE PLIOBOND 1063
	ADHESIVE PLIOBOND 1177
	ADHESIVE PLIOBOND 1240
	ADHESIVE PLIOBOND 20
	ADHESIVE PLIOBOND 2000
	ADHESIVE PLIOBOND 2001
	ADHESIVE PLIOBOND 2003
	ADHESIVE PLIOBOND 2004
	ADHESIVE PLIOBOND 2005
	ADHESIVE PLIOBOND 2007
	ADHESIVE PLIOBOND 2011
	ADHESIVE PLIOBOND 2014
	ADHESIVE PLIOBOND 2015
	ADHESIVE PLIOBOND 2021

MANUFACTURER	DESIGNATION
GOODYEAR	ADHESIVE PLIOBOND 2024
	ADHESIVE PLIOBOND 2030
	ADHESIVE PLIOBOND 2033
	ADHESIVE PLIOBOND 2221
	ADHESIVE PLIOBOND 30
	ADHESIVE PLIOBOND 30HT
	ADHESIVE PLIOBOND 40
	ADHESIVE PLIOBOND 4000
	ADHESIVE PLIOBOND 4007
	ADHESIVE PLIOBOND 4014
	ADHESIVE PLIOBOND 4015
	ADHESIVE PLIOBOND 4222
	ADHESIVE PLIOBOND 4237
	ADHESIVE PLIOBOND 4245
	ADHESIVE PLIOBOND 4254
	ADHESIVE PLIOBOND 4275
	ADHESIVE PLIOBOND 4290
	ADHESIVE PLIOBOND 5000
	ADHESIVE PLIOBOND 5001
	ADHESIVE PLIOBOND 5002
	ADHESIVE PLIOBOND 5013
	ADHESIVE PLIOBOND 5015
	ADHESIVE PLIOBOND 5019
	ADHESIVE PLIOBOND 5037
	ADHESIVE PLIOBOND 7001
	ADHESIVE PLIOBOND 7003
	ADHESIVE PLIOBOND 7005
	ADHESIVE PLIOBOND 8000
	ADHESIVE PLIOBOND 8001
	ADHESIVE PLIOBOND 8003
	ADHESIVE PLIOBOND 8004
	ADHESIVE PLIOBOND 8005
	ADHESIVE PLIOBOND 9002
	ADHESIVE PLIOBOND 9005
	ADHESIVE RUBINATE M/VITEL PE307
	COATING VITON B50/ZIPPER NOMEX
	COMPOSITE KEVLAR/VITON
	COMPOSITE VITON B50/NOMEX RF41
	COMPOSITE VITON B50/POLYESTER
	COMPOSITE VITON/POLYEST DY793
	FABRIC KELVAR 29
	FABRIC KEVLAR RF443/TAPE RF282
	FABRIC NOMEX GAC-RF-444
	FABRIC NOMEX RF444/TAPE RF282
	FABRIC POLYESTER RF415
	FLEX ELEMENT S/N-4
	PLASTIC CLEARSTUF 1006
	PLASTIC CLEARSTUF 5901
	PLASTIC CLEARSTUF 7202
	PLASTIC CLEARSTUF 7204
	PLASTIC CLEARSTUF 7207
	PLASTIC CLEARSTUF 8002
	PLASTIC CLEARSTUF 8006
	PLASTIC CLEARSTUF 8403
	PLASTIC CLEARSTUF 9504

MSFC-HDBK-527 REV F 9999942 0006908 3

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
GOODYEAR	PLASTIC CLEARSTUF 9506
	PLASTIC PE 100
	PLASTIC PE 2000
	PLASTIC PE 207F
	PLASTIC PE 222
	PLASTIC PE 307TS
	PLASTIC VITUF 6204
	PLASTIC VITUF 6209
	PLASTIC VITUF 7002
	PLASTIC VITUF 7800G
	PLASTIC VITUF 9505
	PLASTIC VPE-4583A
	PLASTIC VPE-4670A
	PLASTIC VPE-5253
	PLASTIC VPE-5833A
	PLASTIC VPE-5987A
	PLASTIC VPE5066A
	RUBBER VITON B50/DZ700610
	RUBBER VITON B50/DZ70D610
	RUBBER VITON B50/DZ70D613
	SHOE HEEL NEOLITE
	TAPE NOMEX RF466/COATING VITON B50
	ZIPPER NOMEX COATED WITH RTV 6-1104
	ZIPPER NOMEX VF106
	ZIPPER NOMEX/COATING VITON B50
GORDON SERV-RITE	WIRE ELEC THERMOCOUPLE FIBERGLASS
GOSS PLASTIC FILM	FILM VINYL GAUGE 8G
GOULD	BATTERY CELL ZN-AIR 630HP
	BATTERY NI/CD RECHARGE 7.0SC
	PAPER CHART TYPE 58340
GRACE CHEMICAL	BAG NYLON MESH X-1591
GRAPHTEX INC	COATING DURACHEM 13905 EPOXY
	COATING DURACHEM 13905/DURACH 415
GREENE TWEED CO	PLASTIC GTC160
	RUBBER NITRILE 160
	RUBBER NITRILE 972
	RUBBER NITRILE/TFE TEFLON
GREER HYDRAULICS	RUBBER NITRILE
GRID COMPUTER CO	CABLE IEEE 188
GROENDYK	RUBBER SILICONE GROENDYK 7504
	SPONGE RUBBER SILICONE
GROVE SPECIALTIES	SEALANT GS1450 POURABLE
GROVE VALVE & REGULATOR	KEL-F 81
	RUBBER VITON 871
GRUMMAN	RUBBER URETHANE CYANAPRENE 3090
GSA	BAG PLASTIC INTERLOCKING CLOSR
	BAG ZIP LOCK VINYL ACETATE
	CUFFS ROLL-ON
	INK COLITHO 0691-19003/JCP E20
	INK DICK-B-4020C ON JCP E20
	LABEL IDENTIFICATION UCD CLIPS 0109-22061-01
	LABELS PAPER P/S
	PAPER BOND HIGH RAG CONTENT
	PENCIL GREASE ON LP4 FILM

MANUFACTURER	DESIGNATION
GSA	PENCIL GREASE WITH VELCRO
	RUBBER 4930-00-946-2916
	TEFLON TFE VIRGIN
	WIRE ELEC KYNAR PVF
	WRISTLETS P/N A7L-101121-01
GTE	CABLE HIGH VOLTAGE RUBBER SILICONE INSULATED WITH VITON SLEEVING
GUDEBROD BROS SILK	CORD DACRON 1101 P2
	LACING CORD GUDEBROD DPT-H DACRON
	LACING TAPE BRAID NYLON
	LACING TAPE GLASS/TFE
	LACING TAPE GUDE-LACE
	LACING TAPE GUDE-SPACE 18DPT-H
	LACING TAPE GUDETEMP 718Z NOMEX
	LACING TAPE GUDETEMP 723G NOMX
	LACING TAPE NOMEX 1251
	LACING TAPE NOMEX 1251P
	LACING TAPE NOMEX 1251V
	LACING TAPE NOMEX 1251VC
	LACING TAPE NOMEX 1316
	LACING TAPE NOMEX 1317Z
	LACING TAPE NOMEX 1318X5
	LACING TAPE NOMEX 1342-300
	LACING TAPE NOMEX 1342G
	LACING TAPE NOMEX GUDE-TEMP
	LACING TAPE NOMEX RD1251Z
	LACING TAPE NOMEX/VITON 1342C
	LACING TAPE NOMEX/VITON 1342V
	LACING TAPE NOMEX/VITON 1342VC
	LACING TAPE NYLON
	LACING TAPE NYLON/RUBBER 18H
	LACING TAPE PBI/VITON 1330
	LACING TAPE PBI/VITON 1330V
	LACING TAPE PBI/VITON 1330VC
	LACING TAPE POLYESTER/DACRON
	LACING TAPE TEMP-LACE H/276H
	LACING TAPE TFE 2560
	LACING TAPE TFE/RUBBER H 231H
	TAPE BUNDLING GLASS FABRIC
	WEBBING 22DPT-H
GULF OIL	LUBE GREASE HYDROCARBON AF419
	LUBE GREASE HYDROCARBON AF903
GULF WANDES	PLASTIC CHEMTROL PP TYPE 1
	PLASTIC CPVC TYPE 4
	PLASTIC DERAKANE 470
	PLASTIC DERAKANE 510N
	PLASTIC FLOUROSINT 207
	PLASTIC FLOUROSINT 500
	PLASTIC FLOUROSINT TFE
	PLASTIC FOAMEX
	PLASTIC KYNAR
	PLASTIC KYNAR PVDF
	PLASTIC MC901
	PLASTIC MICARTA 20005
	PLASTIC MICARTA 20007

MSFC-HDBK-527 REV F 9999942 0006909 5

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
GULF WANDES	PLASTIC MICARTA 213
	PLASTIC MICARTA 219
	PLASTIC MICARTA 221
	PLASTIC MICARTA 223
	PLASTIC MICARTA 238
	PLASTIC MICARTA 254
	PLASTIC MICARTA 259-2
	PLASTIC MICARTA 262
	PLASTIC MICARTA 281
	PLASTIC MICARTA 286
	PLASTIC MICARTA 400
	PLASTIC MICARTA 423
	PLASTIC MICARTA 429
	PLASTIC MICARTA 431
	PLASTIC MICARTA 496
	PLASTIC MICARTA 51
	PLASTIC MICARTA 51F33
	PLASTIC MICARTA 51F60
	PLASTIC MICARTA 51P77
	PLASTIC MICARTA 51P88
	PLASTIC MICARTA 5A2
	PLASTIC MICARTA 5A3
	PLASTIC MICARTA 5A4
	PLASTIC MICARTA 76 5A1
	PLASTIC MICARTA 79
	PLASTIC MICARTA 91
	PLASTIC MICARTA 97
	PLASTIC MICARTA H09454
	PLASTIC MICARTA H12426
	PLASTIC MICARTA H17825
	PLASTIC MICARTA H17900
	PLASTIC MICARTA H18331
	PLASTIC MICARTA H18332
	PLASTIC MICARTA H18333
	PLASTIC MICARTA H18720
	PLASTIC MICARTA H19128
	PLASTIC MICARTA H19242
	PLASTIC MICARTA H19243
	PLASTIC MICARTA H22033
	PLASTIC MICARTA H23655
	PLASTIC MICARTA H23842
	PLASTIC MICARTA H24721
	PLASTIC MICARTA H24907
	PLASTIC MICARTA H25126
	PLASTIC MICARTA H25219
	PLASTIC MICARTA H26000
	PLASTIC MICARTA H2898
	PLASTIC MICARTA H5639
	PLASTIC MICARTA H6-1348
	PLASTIC MICARTA HY1216
	PLASTIC MICARTA HY1293
	PLASTIC MICARTA HY1384
	PLASTIC MICARTA HY1457
	PLASTIC MICARTA HY1527
	PLASTIC MICARTA HY1755
GULF WANDES	PLASTIC MICARTA HY180
	PLASTIC MICARTA HY180-1
	PLASTIC MICARTA HY1806
	PLASTIC MICARTA HY1828
	PLASTIC MICARTA HY1928
	PLASTIC MICARTA HY2055
	PLASTIC MICARTA HY2140
	PLASTIC MICARTA HY2180
	PLASTIC MICARTA HY278
	PLASTIC MICARTA HY290-2
	PLASTIC MICARTA HY512
	PLASTIC MICARTA HY689
	PLASTIC MICARTA HY964
	PLASTIC MONOCAST
	PLASTIC NYLAFLOW
	PLASTIC NYLATRON GSM
	PLASTIC NYLON 101
	PLASTIC PLEXIGLASS 55
	PLASTIC PLEXIGLASS G AND 2 UVA
	PLASTIC PLEXIGLASS K
	PLASTIC POLYPENCE TFE
	PLASTIC POLYPENCO TR-1
	PLASTIC POLYPROPYLENE
	PLASTIC PVC TYPE I
	PLASTIC ULTRA-WEAR UHMPE
	TEFLON TFE 3602
	TEFLON TFE VIRGIN
GULTON INDUSTRIES	CERAMIC DUROCK 101
	CERAMIC DUROCK 117
	CERAMIC DUROCK 17 OR 33
	CERAMIC DUROCK 204
	PIEZD XTLS G1500,G1900 (INORG)
H B FULLER	ADHESIVE ACCUTHANE UR1100
	ADHESIVE FD4207
	ADHESIVE HM0904
	ADHESIVE HM0964
	ADHESIVE HM1357
	ADHESIVE HM1752
	ADHESIVE HM1756
	ADHESIVE RESIWELD 7004
	ADHESIVE RESIWELD 7004/5% CABOSIL
	ADHESIVE RESIWELD FE0004
	ADHESIVE RESIWELD FE0185
	ADHESIVE RESIWELD FE1402
	ADHESIVE RESIWELD FE5050
	ADHESIVE RESIWELD FE6721
	ADHESIVE RESIWELD FE7002 EPOXY
	ADHESIVE RESIWELD FE7005
	ADHESIVE SC2505
	ADHESIVE UR2139
	ADHESIVE UR2170
	ADHESIVE UR2183
H H SMITH	FIBRE VULCANIZED GRADE CH
	RUBBER BUMBER
H O CANFIELD	RUBBER SILICONE 89780

MSFC-HDBK-527 REV F 9999942 0006910 1

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
H P SMITH	PAPER FREEZER WRAP POLYETH COATED
H T L INDUSTRIES	FILM TEFLON FEP T160
HADBAR	GASKET MATERIAL RUBBER SILICONE/NOMEX
	GASKET SILICONE NOMEX HT 46-45
	RUBBER SILICONE HADBAR 3250
	RUBBER SILICONE HADBAR 3254
	RUBBER SILICONE HARDNESS SHORE "A" 55-65
	RUBBER SILICONE HB400-50
	RUBBER SILICONE SE4404U WITH SI02 FILLER
HADBAR/CHOMERICS	RUBBER SILICONE SE4404U WITH SI02 FILLER WITH CHOBOND 320 ADHESIVE
HALOCARBON PRODUCTS	INSULATION FOAM POLYSTYRENE/HALOCARBON 6-25 COATED
	INSULATION FOAM POLYSTYRENE/HI VISC BFC FLUID
	LUBE GREASE HALOCARBON 25-5S
	LUBE OIL HALOCARBON 11-14
	LUBE OIL HALOCARBON 11-21S
	LUBE OIL HALOCARBON 6.3
	LUBE OIL HALOCARBON 80-114
	LUBE OIL HALOCARBON MO-10
	LUBE OIL HALOCARBON SERIES 27S
HAMILTON KENT	RUBBER POLYURETHANE SORBOTHANE
	RUBBER POLYURETHANE SORBOTHANE/50
HAMILTON STANDARD	COATING APCO 434/SONITE 41 EPOXY
	HARNESS ASSEMBLY NOMEX BRAIDED 200 DENIER COVER
	HOSE FLEX TEFLON/1% CARBON
	HOSE SILICONE/PBI POS BREATHER
	INSULATION FOAM CEI 10 FLUOROCARBON
	LAMIN EPOXY/BORON/TITANIUM SHEET
	LAMIN EPOXY/CAB-O-SIL
	LAMIN EPOXY/GLASS SVHS 8091T11
	LAMIN EPOXY/GLASS SVHS 8091T13
	LAMIN EPOXY/GLASS SVHS 8091T2
	LAMIN EPOXY/GLASS SVHS 8091T3
	LAMIN EPOXY/GLASS SVHS 8091T4
	LAMIN POLYESTER/GLASS HETRON 92
	MULTI-LAYERED INSULATION BLANKET THERMAL
HAMMOND PLASTICS	PLASTIC POLYPROPYLENE 20% CALCIUM CARBONATE FILLED
	PLASTIC POLYPROPYLENE 20% TALC FILLED
	PLASTIC POLYPROPYLENE 40% CALCIUM CARBONATE FILLED
	PLASTIC POLYPROPYLENE 40% TALC FILLED
	PLASTIC SUPER FLOW 390
	PLASTIC SUPER FLOW 400
	PLASTIC SUPERDENSE 700
	PLASTIC SUPERDENSE 710
	PLASTIC SUPERFLEX 405
	PLASTIC SUPERFLEX 425
	PLASTIC SUPERFLEX 432
	PLASTIC SUPERFLEX 505
	PLASTIC SUPERFLEX 550
	PLASTIC SUPERFLEX FR-1

MANUFACTURER	DESIGNATION
HANDY & HARMAN	FLUX HANDY TYPE B-1
HARDMAN INC	ADHESIVE DOUBLE/BUBBLE EPOXY
	ADHESIVE EPOCAP 13050
	ADHESIVE EPOCAP 3195 WITH EPOCURE S-L
	ADHESIVE EPOWELD 13230
	ADHESIVE EPOWELD 2156 WITH EPOCURE 110
	ADHESIVE EPOWELD 2156 WITH EPOCURE 118
	ADHESIVE EPOWELD 2156 WITH EPOCURE S9
	ADHESIVE EPOWELD 3243 HIGH IMPACT STRENGTH ADHESIVE
	ADHESIVE EPOWELD 3583 WITH EPOCURE S-L HIGH IMPACT STRENGTH ADHESIVE
	ADHESIVE EPOWELD 3650 PASTE FORM HIGH STRENGTH ADHESIVE
	ADHESIVE EPOWELD 7781
	ADHESIVE EPOWELD 7895 HIGH STRENGTH GENERAL PURPOSE ADHESIVE
	ADHESIVE EPOWELD 7903
	ADHESIVE EPOWELD 7982
	ADHESIVE EPOWELD 8173
	ADHESIVE EPOWELD 8185
	ADHESIVE EPOWELD 8200 HIGH IMPACT STRENGTH AD IMPACT STRENGTH ADHESIVE
	ADHESIVE EPOWELD 8269 20 MINUTE SETTING ADHESIVE
	ADHESIVE EPOWELD 9143A THIXOTROPIC FLEXIBLE ADHESIVE
HARRISON MFG	SEALS K-6 LEAD COATED
HARRY GOLDMAN FOAM	SPONGE RUBBER LATEX KOYLON
HARRY SUGARMAN INC	EMBLEM CLOTH US FLAG
HARTEL ENTERPRISE	ADHESIVE 17017 A/B POLYURETHANE
	ADHESIVE HE17017 E-2 KIT
HARTWELL CORP	FASTENER VELCRO LOOP NYLON 80 WITH PS 0172
	FASTENER VELCRO NOMEX HAQ 12-2 LOOP WITH 6-1015 NEOPRENE ADHESIVE
	FASTENER VELCRO NOMEX HI-AIR HAQ 12-2-200-SAI LOOP AND 12-1-200 HOOK
	FASTENER VELCRO NYLON HOOK 80 WITH PS 0172
	FASTENER VELCRO NYLON HOOK AND LOOP 80 BACKING PS 0172
HASBROUCK PLASTICS INC	PLASTIC RESIOUR AR
	PLASTIC RESIOUR T
	PLASTIC RESTOUR P
	PLASTIC RESTOUR V
HASKON CORPORATION	GASKET MATERIAL HASKON 8099 NOMEX/RUBBER SILICONE
	SEALANT SILICONE/NOMEX HT2002
HAVEG	ADHESIVE EPOXY ER825A
	CABLE ELEC RTM437 CU IMBEDDED IN FEP WITH TEFLON OVERWRAP
	LAMIN CARBON/PHENOLIC 2267-01
	LAMIN CARBON/PHENOLIC 2269-01
	SEALANT SILICONE/DACRON HAVEG F717/720
	WIRE ELEC FEP
	WIRE ELEC FEP/POLYIMIDE TAPE

Information Handling Services, 2000

MSFC-HDBK-527 REV F ■ 9999942 0006911 3 ■

MANUFACTURER	DESIGNATION
HAVEG	WIRE ELEC PYRAD 1000
	WIRE ELEC TEFLON TFE
	WIRE ELEC TFE/ML ENAMEL
HAVEY INSULATION	WIRE ELEC TEFLON TFE
HAWKEYE ENTERPRISES	LACING TAPE HKK KEVLAR 49
HAYSITE DIV., TAYLOR CORP	PLASTIC EFM
	PLASTIC EGP-S
	PLASTIC EHC
	PLASTIC EHG-S
	PLASTIC ESA-S
	PLASTIC ESG-S
	PLASTIC ETR-FR-C
	PLASTIC ETS
	PLASTIC ETS-FR
	PLASTIC ETS-FR-11
	PLASTIC H755
	PLASTIC HAYSITE 12000
	PLASTIC HAYSITE 13600
	PLASTIC HAYSITE 14100
	PLASTIC HAYSITE 16100
	PLASTIC HAYSITE 16600
	PLASTIC HAYSITE 17000
	PLASTIC HAYSITE 18500
	PLASTIC HAYSITE 20000
	PLASTIC HAYSITE 270 FR2
	PLASTIC HAYSITE 30000
	PLASTIC HAYSITE 40000
	PLASTIC HAYSITE 42000
	PLASTIC HAYSITE 43000
	PLASTIC HAYSITE 44000
	PLASTIC HAYSITE 46000
	PLASTIC HAYSITE 47000
	PLASTIC HAYSITE 48000
	PLASTIC HAYSITE 53000
	PLASTIC HAYSITE 60000
	PLASTIC HAYSITE 70000
	PLASTIC HST11
HECT RUBBER CORPORATION	CORD SHOCK RUBBER COVERED NYLON (BUNGEE)
HEINEMAN ELECTRIC CO	CIRCUIT BREAKER HEINEMAN
HELENA RUBINSTEIN	MASCARA EVERY LAST LASH/BROWN
HEMINGWAY BARTLETT	THREAD KEVLAR B132
	THREAD KEVLAR B66
	THREAD POLYESTER BLACK FF
	THREAD POLYESTER GOLD
	THREAD POLYESTER SIZE E
	THREAD POLYESTER STEEL SIZE F
HENKEL	ADHESIVE OMNIFIT 1150
	ADHESIVE OMNIFIT 1350
	ADHESIVE OMNIFIT 1550
	ADHESIVE OMNIFIT 1570
	ADHESIVE OMNIFIT 1710
	ADHESIVE OMNIFIT 1730
	ADHESIVE OMNIFIT 1750
	ADHESIVE OMNIFIT 1790

MANUFACTURER	DESIGNATION
HENKEL	ADHESIVE OMNIFIT INSTANT GASKET 10
	ADHESIVE OMNIFIT INSTANT GASKET 20
	ADHESIVE SICOMET 40
	ADHESIVE SICOMET 50
	ADHESIVE SICOMET 5019
	ADHESIVE SICOMET 5044
	ADHESIVE SICOMET 65
	ADHESIVE SICOMET 7000
	ADHESIVE SICOMET 77
	ADHESIVE SICOMET 7900
	ADHESIVE SICOMET 8200
	ADHESIVE SICOMET 8300
	ADHESIVE SICOMET 8400
	ADHESIVE SICOMET 85
	ADHESIVE SICOMET 8546
	ADHESIVE SICOMET 99
	ADHESIVE UK8202/UK5400
	ADHESIVE VERSAMID 125
	ADHESIVE VERSAMID 140
HERCULES	CARBON FIBER TOW AS4W
	COMPOSITE 5245C RESIN/IMG FIBR
	FABRIC ARGNAMITE GRAPHITE COATED
	FILA WOUND CASE COMP/SEALER
	FILA WOUND CASE COMPONENTS
	LAMIN EPOXY/GRAPHITE
	LAMIN EPOXY/GRAPHITE COATED WITH SMOOTH TEDLAR
	LAMIN EPOXY/GRAPHITE COATED WITH TEXTURED TEDLAR
	MOLD COMPOUND PROFAX 7231
	MOLD COMPOUND PROFAX SE-012
	PLASTIC PROFAX 6323
	PLASTIC PROFAX 6331
	PLASTIC PROFAX 6331NW
	PLASTIC PROFAX 6523
	PLASTIC PROFAX 6524
	PLASTIC PROFAX 65F4-2
	PLASTIC PROFAX 65F4-4
	PLASTIC PROFAX 65F5-2
	PLASTIC PROFAX 65F5-4
	PLASTIC PROFAX 6723
	PLASTIC PROFAX 6823
	PLASTIC PROFAX 7523
	PLASTIC PROFAX 75F4-2
	PLASTIC PROFAX 75F4-4
	PLASTIC PROFAX 75F5-2
	PLASTIC PROFAX 75F5-4
	PLASTIC PROFAX 7623
	PLASTIC PROFAX 7624
	PLASTIC PROFAX 7723
	PLASTIC PROFAX 7823
	PLASTIC PROFAX 8523
	PLASTIC PROFAX 8623
	PLASTIC PROFAX PD064
	PLASTIC PROFAX PD195

MSFC-HDBK-527 REV F 9999942 0006912 5

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
HERCULES	PLASTIC PROFAX SB222PM
	RUBBER SILICONE 0117 DACRON REINFORCED
	RUBBER SILICONE H567
	RUBBER SILICONE HERCULES H564
	SEALANT SILICONE/NOMEX HT2002
HERCULITE CORP	ADHESIVE CVV
	FABRIC HERCULITE 80 NYLON
	FABRIC NYLON/PVC HERCULITE 20
HEWLETT-PACKARD	COATING INK ON PAPER FROM HP2225A
	PAPER HP INKJET 92261N
HEXCEL	ADHESIVE EPOLITE 5313 EPOXY RESIN
	ADHESIVE HEXABOND 3 FILM
	ADHESIVE URALITE 3124 POLYURETHANE RESIN
	ADHESIVE URALITE 3139 POLYURETHANE ORANGE
	ATTENUATION PAD HRH-10 1/8-4.0
	COATING 02-GY-3 WITH ARAMID LAMIN
	COATING 02-GY-3 WITH KEVLAR LAMIN
	CONFIG SEE 06475/05325
	CORD CELION 6000 EPOXY/CARBON
	CORE HONEYCOMB/ALUMINUM FACE PLATES
	ADHESIVE BONDED
	CORE HRN-10 NOMEX/PHENOLIC
	CORE HRP/HFT GLASS/PHENOLIC HC
	DUCT GLASS/POLYIMIDE 7781/F178
	LAMIN EPOXY/ARAMID
	LAMIN EPOXY/ARAMID F164
	LAMIN EPOXY/GLASS
	LAMIN EPOXY/GLASS F164
	LAMIN EPOXY/GLASS F164-1
	LAMIN EPOXY/GLASS F164-1/7781
	LAMIN EPOXY/GLASS F164/7781
	LAMIN EPOXY/GLASS WITH HRH
	LAMIN EPOXY/GRAPHITE F263
	LAMIN EPOXY/KEVLAR F155
	LAMIN EPOXY/KEVLAR F161
	LAMIN EPOXY/KEVLAR F164-1/181
	LAMIN EPOXY/KEVLAR F164/120 KEVLAR 49
	LAMIN F120-150-1P20
	LAMIN F161-1581/F50
	LAMIN F161-173G/7781 EPOXY/GLASS
	LAMIN F161-173G/7781/HS8171
	LAMIN F164/181 KEVLAR-49
	LAMIN GRAPHITE HFT-G HONEYCOMB CORE
	LAMIN POLYIMIDE/GLASS
	LAMIN POLYIMIDE/GLASS F174
	LAMIN POLYIMIDE/GLASS F178/7781
	LAMIN POLYIMIDE/RESIN X PLY
	PAD ATTENUATION HFT 3/16 4.0
	PLASTIC EPOLITE 3300
	PLASTIC EPOLITE 3301
	PLASTIC EPOLITE 3302
	PLASTIC EPOLITE 3306
	PLASTIC EPOLITE 3306-1
	PLASTIC EPOLITE 3354
	PLASTIC EPOLITE 3362
HEXCEL	POTTING COMPOUND REZOLIN 185N POLYURETHANE
	RUBBER URALITE 3121S
	RUBBER URALITE 3130
	RUBBER URALITE 3136
	RUBBER URALITE 3138
	RUBBER URALITE 3140
	RUBBER URALITE 3142
	RUBBER URALITE 3148
	RUBBER URALITE 3150
	RUBBER URALITE 3154
HI LOK	FASTENER HL410V
HI SHEER	PROPELLANT PELLET
HI TEMP INSULATION	INSULATION AFRSI WITH SILANE Z6070
	INSULATION BLANKET MC364-0011
	INSULATION GLASS/PHENOLIC M-P-AA-W
	INSULATION GLASS/SILICONE M-S-AA
	INSULATION SILICONE THERMAL
	TAPE PVF OT6
HIAWATHA RUBBER CO	RUBBER VITON A V86-678
HILLCOR	MOLD COMPOUND CELLU/ACETATE BUTYRAT
HITCO	ADHESIVE NEOPRENE 61015
	FABRIC PHENOLIC/CARBON FM5055G
	FABRIC SILICA C1154-48
	FELT REFRASIL B100 SILICA
	INSULATION TG15000/MYLAR/FEP TAPE
	INSULATION TG15000/SCOTCH 853 TAPE
	INSULATION TG15000/SILICONE/GLASS BINDER
	MOLD COMPOUND DIAL 52-01 DAP
	MULTI-LAYERED INSULATION HITCO TG15000/ G134600 GOLDIZED KAPTON
HOECHST FIBERS	FABRIC TREVIRA POLYEST 203 GRN
	FABRIC TREVIRA POLYEST 207 GRN
	FABRIC TREVIRA POLYESTER 271
	PLASTIC HOSTAFLON TF
	PLASTIC HOSTAFLON TF1665
	PLASTIC HOSTAFLON TF2024
	PLASTIC HOSTAFLON TF2026
	PLASTIC HOSTAFLON TF2051
	PLASTIC HOSTAFLON TF2053
	PLASTIC HOSTAFLON TF2071
	PLASTIC HOSTAFLON TF2103
	PLASTIC HOSTAFLON TF4103
	PLASTIC HOSTAFLON TF4105
	PLASTIC HOSTAFLON TF4215
	PLASTIC HOSTAFLON TF4303
	PLASTIC HOSTAFLON TF4406
	PLASTIC HOSTALEN
	PLASTIC HOSTALEN LD
	PLASTIC HOSTALEN PP
	PLASTIC HOSTALIT
	PLASTIC HOSTALIT Z
	PLASTIC HOSTAPOT
	PLASTIC HOSTAPULP
	PLASTIC HOSTYREN
HOKE	HOKE MULTIMITE 5-WAY BALL VALVE

MSFC-HDBK-527 REV F 9999942 0006913 7

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
HOLICKS INC	FABRIC NAMETAGS
HOLLINGSWORTH & VOSE	FIBER HE1051 GLASS/ACRY BIND
HOMALITE CORP	HOMALITE H-911 POLYESTER
HOME IMPROVEMENT PROD	ADHESIVE DAP FUNTAK
HONEYWELL	LAMIN EPOXY/GLASS STRIPPED
	MICRO-SWITCH 12TL1-3
	MICRO-SWITCH 14TL1-3
HOOKER CHEMICAL	FILM RUCOTHANE CO-A5069 POLYURETHANE
	FILM RUCOTHANE CO-A5154
	LUBE FLUOROLUBE GRADE FS5
	LUBE OIL FLUOROLUBE LG160
	MOLD COMPOUND DUREZ 11844 BLK
	MOLD COMPOUND DUREZ 11864 PHENOLIC
	PLASTIC DUREZ 111
	PLASTIC DUREZ 111 BLACK
	PLASTIC DUREZ 111 BROWN
	PLASTIC DUREZ 115
	PLASTIC DUREZ 11540
	PLASTIC DUREZ 118
	PLASTIC DUREZ 118 BLACK
	PLASTIC DUREZ 118 BROWN
	PLASTIC DUREZ 123
	PLASTIC DUREZ 123 BLACK
	PLASTIC DUREZ 123 BROWN
	PLASTIC DUREZ 13124
	PLASTIC DUREZ 13856
	PLASTIC DUREZ 13856AF
	PLASTIC DUREZ 145
	PLASTIC DUREZ 145 BLACK
	PLASTIC DUREZ 145 BROWN
	PLASTIC DUREZ 14900
	PLASTIC DUREZ 152
	PLASTIC DUREZ 152 BLACK
	PLASTIC DUREZ 152 BROWN
	PLASTIC DUREZ 153
	PLASTIC DUREZ 153 BLACK
	PLASTIC DUREZ 153 BROWN
	PLASTIC DUREZ 156
	PLASTIC DUREZ 157
	PLASTIC DUREZ 16038
	PLASTIC DUREZ 161
	PLASTIC DUREZ 16378
	PLASTIC DUREZ 165
	PLASTIC DUREZ 17080
	PLASTIC DUREZ 17156
	PLASTIC DUREZ 17702
	PLASTIC DUREZ 18420
	PLASTIC DUREZ 18441
	PLASTIC DUREZ 18683
	PLASTIC DUREZ 1898
	PLASTIC DUREZ 21028
	PLASTIC DUREZ 21206
	PLASTIC DUREZ 21206 BLACK
	PLASTIC DUREZ 21206 BROWN
	PLASTIC DUREZ 21210
HOOKER CHEMICAL	PLASTIC DUREZ 21372
	PLASTIC DUREZ 22251
	PLASTIC DUREZ 22257 BLACK
	PLASTIC DUREZ 22257 BROWN
	PLASTIC DUREZ 22486
	PLASTIC DUREZ 22761 DAP
	PLASTIC DUREZ 22787
	PLASTIC DUREZ 23410
	PLASTIC DUREZ 23570
	PLASTIC DUREZ 24060
	PLASTIC DUREZ 24150
	PLASTIC DUREZ 24337
	PLASTIC DUREZ 24668
	PLASTIC DUREZ 24776 DAP
	PLASTIC DUREZ 24776 GRAY
	PLASTIC DUREZ 24776 GREEN
	PLASTIC DUREZ 265
	PLASTIC DUREZ 27398
	PLASTIC DUREZ 27962
	PLASTIC DUREZ 28615
	PLASTIC DUREZ 29053
	PLASTIC DUREZ 29237
	PLASTIC DUREZ 29276
	PLASTIC DUREZ 29281 DAP
	PLASTIC DUREZ 29429
	PLASTIC DUREZ 29502
	PLASTIC DUREZ 30169
	PLASTIC DUREZ 30270
	PLASTIC DUREZ 30417
	PLASTIC DUREZ 30614 BLACK
	PLASTIC DUREZ 30614 GREEN
	PLASTIC DUREZ 30645
	PLASTIC DUREZ 3065
	PLASTIC DUREZ 30698
	PLASTIC DUREZ 30725
	PLASTIC DUREZ 30806
	PLASTIC DUREZ 30959
	PLASTIC DUREZ 31219
	PLASTIC DUREZ 31375 POLY
	PLASTIC DUREZ 31572 POLY
	PLASTIC DUREZ 31735
	PLASTIC DUREZ 3948
	PLASTIC DUREZ 740
	PLASTIC DUREZ 791
	PLASTIC DUREZ S1-75 DAP
HOOVER CO	HOSE PLASTIC/SILICONE RUBBER
	VACUUM CLEANER HANDIVAC II
HOWE IND	LAMIN POLYIMIDE HI3003
	LAMIN POLYIMIDE/GLASS HI3000
HUBBELL	CONNECTOR/CABLE
HUGHES AIRCRAFT	ADHESIVE MEL 20
	CONNECTOR ELECTRICAL
	CONNECTOR S-L-C28804-100-3N
	INSULATION BLANKET DP50392 TYPE 2 MYLAR/ KAPTON

MSFC-HDBK-527 REV F 9999942 0006914 9

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
HUGHES AIRCRAFT	INSULATION BLANKET DP50392 TYPE 3 MYLAR/ KAPTON/GLASS
	INSULATION BLANKET DP50392 TYPE 8 KAPTON/ GLASS
	KIT FLIGHT EXPERIMENT CARRY-ON
	LAMIN EPOXY/KEVLAR CE342
	LAMIN HONEYCOMB LEASAT ANTENNA
	PANEL HONEYCOMB/COATING CTL 15
	PCB CONNECTOR/VALOX 420/RYTON
	WIRE ELEC FEP WITH POLYIMIDE TAPE
	WIRE ELEC FLEXIBLE PRINTED/KAPTON
	WIRE ELEC TEFLON TFE
HUILES GOUDRONS&DERI	INSULATION FOAM PHENEXPAN P40/P80
HUNTSMAN CHEMICAL	PLASTIC HUNTSMAN 201
	PLASTIC HUNTSMAN 202
	PLASTIC HUNTSMAN 203
	PLASTIC HUNTSMAN 206
	PLASTIC HUNTSMAN 208
	PLASTIC HUNTSMAN 210
	PLASTIC HUNTSMAN AH703
	PLASTIC HUNTSMAN AH721M
	PLASTIC HUNTSMAN AH731
	PLASTIC HUNTSMAN DP3037
	PLASTIC HUNTSMAN DP351HF
	PLASTIC HUNTSMAN DP355
	PLASTIC HUNTSMAN HCC201
	PLASTIC HUNTSMAN HCC208
	PLASTIC HUNTSMAN HCC271
	PLASTIC HUNTSMAN HCC360
	PLASTIC HUNTSMAN HCC50
	PLASTIC HUNTSMAN HCC702
	PLASTIC HUNTSMAN HCC705
	PLASTIC HUNTSMAN HCC707
	PLASTIC HUNTSMAN HCC730
	PLASTIC HUNTSMAN HCC760
	PLASTIC HUNTSMAN HCC765
	PLASTIC HUNTSMAN HCC779
	PLASTIC HUNTSMAN HCC817
	PLASTIC HUNTSMAN HCC840
	PLASTIC HUNTSMAN HCC850
	PLASTIC HUNTSMAN HCC851
	PLASTIC HUNTSMAN PS312
	PLASTIC HUNTSMAN PS314
	PLASTIC HUNTSMAN PS316
	PLASTIC HUNTSMAN PS318
	PLASTIC HUNTSMAN PS331
	PLASTIC HUNTSMAN PS333
	PLASTIC HUNTSMAN PS335
	PLASTIC HUNTSMAN PS338
	PLASTIC HUNTSMAN PS345
	PLASTIC HUNTSMAN PS350
	PLASTIC HUNTSMAN PS351
	PLASTIC HUNTSMAN SEP15
HY-CAL	CERAMIC CEMENT PS-1027
	WIRE ELEC FEP
HY-CAL	WIRE ELEC TEFLON TFE
HYDE PARK CHEMICAL	COATING TUFF-HYDE TEFLON
HYDRO AIRE	LAMIN EPOXY/GLASS/DC3140 COATED
HYGENIC, CORP	RUBBER LATEX DENTAL DAM
HYSOL DEXTER	ADHESIVE EA934 EPOXY
HYSOL/DEXTER	ADHESIVE 1 EC1500
	ADHESIVE 1 EC2500
	ADHESIVE 1 EC5
	ADHESIVE 1 EC50
	ADHESIVE 1 EC90
	ADHESIVE 1 MC100
	ADHESIVE 1 MC150
	ADHESIVE 1 MC50
	ADHESIVE 2 C100
	ADHESIVE 2 C50
	ADHESIVE 2 C500
	ADHESIVE 3 CI100
	ADHESIVE 3 CI1000
	ADHESIVE 3 ST1000
	ADHESIVE 3 ST5
	ADHESIVE 4144/3496 EPOXY
	ADHESIVE ADX3103.1 EPOXY
	ADHESIVE ADX3111-1 EPOXY
	ADHESIVE ARMSTRONG A5-4318/H3486 EPOXY
	ADHESIVE ARMSTRONG A7-4322
	ADHESIVE ARMSTRONG A8-4219/H2-3404 EPOXY
	ADHESIVE C15-015 A/B EPOXY
	ADHESIVE C7-4248 EPOXY
	ADHESIVE C9-4198/H2-3561
	ADHESIVE C9-4210 AND 4215/H3469 EPOXY
	ADHESIVE C9-42101/H3561 EPOXY
	ADHESIVE C9-4215/H3561 EPOXY
	ADHESIVE CCX536/3561
	ADHESIVE EA1347
	ADHESIVE EA6 EPOXY
	ADHESIVE EA8 EPOXY
	ADHESIVE EA815
	ADHESIVE EA828/DER732/AEP/CABOSIL
	ADHESIVE EA828/DTA/AL POWDER EPOXY
	ADHESIVE EA828/VERSAMID 115 EPOXY
	ADHESIVE EA828/VERSAMID 125/FILLED
	ADHESIVE EA828/VERSAMID 140 1/1BW
	ADHESIVE EA901/A1
	ADHESIVE EA901/B1
	ADHESIVE EA901/L3
	ADHESIVE EA901NA/B1
	ADHESIVE EA901NA/L3
	ADHESIVE EA911F
	ADHESIVE EA913 EPOXY
	ADHESIVE EA919 A/B EPOXY
	ADHESIVE EA919/L3
	ADHESIVE EA9210H PR 10%
	ADHESIVE EA9210H PR 5%
	ADHESIVE EA921NA EPOXY
	ADHESIVE EA9228 PRIMER

MSFC-HDBK-527 REV F 9999942 0006915 0

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
HYSOL/DEXTER	ADHESIVE EA926 EPOXY
	ADHESIVE EA929
	ADHESIVE EA9306
	ADHESIVE EA9307 EPOXY
	ADHESIVE EA9309 EPOXY
	ADHESIVE EA9309-2
	ADHESIVE EA9309-3NA
	ADHESIVE EA9320NA EPOXY
	ADHESIVE EA9321 EPOXY
	ADHESIVE EA9323
	ADHESIVE EA9326 EPOXY
	ADHESIVE EA9330 EPOXY
	ADHESIVE EA934NA EPOXY
	ADHESIVE EA9351
	ADHESIVE EA940 EPOXY
	ADHESIVE EA9414 EPOXY
	ADHESIVE EA9421
	ADHESIVE EA946
	ADHESIVE EA946/L3-2
	ADHESIVE EA956 EPOXY
	ADHESIVE EA960
	ADHESIVE EA9601 EPOXY
	ADHESIVE EA960F
	ADHESIVE EA9628NW FILM
	ADHESIVE EA9814NA
	ADHESIVE EC847 NITRILE BASED
	ADHESIVE EE4215/H3469
	ADHESIVE EPOXY PATCH KIT
	ADHESIVE EPOXY PATCH KIT 0151 CLEAR A/B
	ADHESIVE EPOXY PATCH KIT 1105
	ADHESIVE EPOXY PATCH KIT 1C
	ADHESIVE EPOXY PATCH KIT 309
	ADHESIVE EPOXY PATCH KIT 3X
	ADHESIVE EPOXY PATCH KIT 56C WHITE
	ADHESIVE EPOXY PATCH KIT 608
	ADHESIVE EPOXY PATCH KIT 615
	ADHESIVE EPOXY PATCH KIT 6C
	ADHESIVE EPOXY PATCH KIT 907 GREEN
	ADHESIVE EPOXY PATCH KIT 9340
	ADHESIVE EPOXY R82038/HD3475
	ADHESIVE EPOXY SILVER FILLED K20
	ADHESIVE FOAM EA9814 EPOXY
	ADHESIVE HYSOL 4351/3469
	ADHESIVE HYSOL EE4183
	ADHESIVE HYSOL EPOXY
	ADHESIVE HYSOL RE2039
	ADHESIVE KE4238
	ADHESIVE KE4239
	ADHESIVE KO1002
	ADHESIVE KO109
	ADHESIVE KO308
	ADHESIVE KO309
	ADHESIVE KS0001
	ADHESIVE KS0002
	ADHESIVE KS0003

MANUFACTURER	DESIGNATION
HYSOL/DEXTER	ADHESIVE KS14
	ADHESIVE KS4007
	ADHESIVE KS4008
	ADHESIVE POLYURETHANE C7-4247
	ADHESIVE R92039/H23490 EPOXY AB/BG
	ADHESIVE RE2039/H3537 EPOXY
	ADHESIVE THERMOFOAM 3008
	ADHESIVE THERMOFOAM 3028
	ADHESIVE THERMOFOAM 3050
	ADHESIVE THERMOFOAM 3056
	ADHESIVE XEA9369
	ADHESIVE XEA9394 EPOXY
	COATING 7X983 SILICONE 3709-A13
	COATING ACRYLIC PC20/20M
	COATING DK403 EPOXY DRY POWDER
	COATING EPOXY SR1000 SOLDER RESIS
	COATING METALOX/31G6/11X2/50C3
	COATING PC 29/29M POLYURETHANE
	COATING PC12-007 EPOXY
	COATING PC17/17M POLYURETHANE
	COATING PC18/18M POLYURETHANE
	INK CAT-L-INK 50-100R/20
	INK CAT-L-INK 50-110/20
	INK CAT-L-INK 50-403R/20
	INK CAT-L-INK 50-508R/20
	INK CAT-L-INK 50-70 EPOXY
	INK CAT-L-INK 50-700/1
	INK CAT-L-INK 50-700R/20
	INK CAT-L-INK 50-700R/9
	INK CAT-L-INK 50-710/20.
	INK CAT-L-INK 50-770
	INK EPOXY 128-45C BLACK
	INK L-O-N SERIES MARKING
	INK WARNOWINK M-9-N WITH DEPTHANE GLOSS
	NO. 1 OVERCOAT
	INK WORNOW 50-100R/9 WHITE
	INK WORNOW SERIES M GR/RED/BLU
	INK WORNOWINK M-6-N/CAT A
	INK WORNOWINK M-9-N/100 PARTS BY WEIGHT OF
	INK BLENDED WITH 4.9 PARTS BY WEIGHT OF C
	ATALYST
	INK WORNOWINK M-O-N/CAT A
	PLASTIC C60 STD
	PLASTIC C61 STD
	PLASTIC C9-4183/HD3485
	PLASTIC C9-4186/HD3485
	PLASTIC DK17
	PLASTIC DK17-01
	PLASTIC DK17-05
	PLASTIC DK18-05
	PLASTIC DK27
	PLASTIC DK28
	PLASTIC DK30
	PLASTIC DK32
	PLASTIC E50047

MSFC-HDBK-527 REV F 9999942 0006916 2

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
HYSOL/DEXTER	PLASTIC EE0036/HD3561
	PLASTIC EE0036/HD3615
	PLASTIC EE0067/HD3404
	PLASTIC EE0067/HD3561
	PLASTIC EE0067/HD3615
	PLASTIC EE0149/HD3561
	PLASTIC EE1067/HD3561
	PLASTIC EE1068/HD0242
	PLASTIC EE1068/HD0243
	PLASTIC EE1087/HD3404
	PLASTIC EE1087/HD3561
	PLASTIC EE1087/HD3615
	PLASTIC EE4143/HD3404
	PLASTIC EE4143/HD3475 FILLED
	PLASTIC EE4143/HD3490
	PLASTIC EE4183/HD0242
	PLASTIC EE4183/HD0243
	PLASTIC EE4183/HD3404
	PLASTIC EE4183/HD3410
	PLASTIC EE4183/HD3469
	PLASTIC EE4183/HD3475 FILLED
	PLASTIC EE4183/HD3485
	PLASTIC EE4183/HD3490
	PLASTIC EE4183/HD3537
	PLASTIC EE4183/HD3561
	PLASTIC EE4183/HD3615
	PLASTIC EE4183/HD3719
	PLASTIC EE4183/HD3840
	PLASTIC EE4186/HD3537
	PLASTIC EE4799/HD3596
	PLASTIC EO0102
	PLASTIC EO0103
	PLASTIC EO0104
	PLASTIC EO0105
	PLASTIC EO0106
	PLASTIC EO0107
	PLASTIC EO0108
	PLASTIC EO0109
	PLASTIC EO0110
	PLASTIC EO1016
	PLASTIC EO1035
	PLASTIC EO1038
	PLASTIC ES0002
	PLASTIC ES0007
	PLASTIC ES0032
	PLASTIC ES0033
	PLASTIC ES0042
	PLASTIC ES0043
	PLASTIC ES0047
	PLASTIC ES0052
	PLASTIC ES0269
	PLASTIC ES0329
	PLASTIC ES4212
	PLASTIC ES4312
	PLASTIC ES4322

MANUFACTURER	DESIGNATION
HYSOL/DEXTER	PLASTIC ES4323
	PLASTIC ES4325
	PLASTIC ES4326
	PLASTIC ES4412
	PLASTIC LE1006/HD3831
	PLASTIC LE4341/1HD3201
	PLASTIC LE5301/1HD3824
	PLASTIC LE5301/HD3201
	PLASTIC LE6019/HD3469
	PLASTIC LE6328/HD3201
	PLASTIC MG15F
	PLASTIC MG18
	PLASTIC MG25F
	PLASTIC MG25F-LMP
	PLASTIC MG25F-LMP(F)
	PLASTIC MG25F-LMP-1
	PLASTIC MG35F
	PLASTIC MG35F-01
	PLASTIC MG6-0260
	PLASTIC MG8F-0134
	PLASTIC MH19F-0217
	PLASTIC MH19F-0294
	PLASTIC MH2-W254
	PLASTIC MH6-W588
	PLASTIC MH9-02 BLACK
	PLASTIC RE2038/HD3404
	PLASTIC RE2038/HD3475 UNFILLED
	PLASTIC RE2038/HD3490
	PLASTIC RE2039/HD0243
	PLASTIC RE2039/HD242
	PLASTIC RE2039/HD3404
	PLASTIC RE2039/HD3410
	PLASTIC RE2039/HD3469
	PLASTIC RE2039/HD3475 UNFILLED
	PLASTIC RE2039/HD3561
	PLASTIC RE2039/HD3615
	PLASTIC RE2039/HD3719
	PLASTIC RE2039/HD3840
	PLASTIC RER2039/HD3490
	POTTING COMPOUND C9-4210/H2-3561/2775
	POTTING COMPOUND C9W690/HD3615
	POTTING COMPOUND EE0004/HD3561
	POTTING COMPOUND EE4215/HD3615
	PRINTED WIRING BOARD COPPER CLAD/POLYIMIDE GLASS/CAT-L-INK 50-100 MARKING 1 TO 3 MIL S THICK/URALANE 5075 CONFORMAL COATING 3 TO 5 MILS THICK
	ROD CP2-4289
	RUBBER US0059
	RUBBER US0066
	RUBBER US0075
	RUBBER US0081
	RUBBER US0082
	RUBBER US0083
	RUBBER US0084

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
HYSOL/DEXTER	SEALANT URETHANE S183026
HYSOL/DEXTER	ADHESIVE EA913NA
I M I TECH CORP	INSULATION FOAM SOLIMIDE FF201 POLYIMIDE
	INSULATION FOAM SOLIMIDE TA301 POLYIMIDE
I W INDUSTRIES INC	ADHESIVE BRUTEM 14
	ADHESIVE BRUTEM 17
	ADHESIVE BRUTEM 33
	ADHESIVE BRUTEM 506
	ADHESIVE BRUTEM 78
	ADHESIVE BRUTEM 91
	ADHESIVE BRUTEM 92
	ADHESIVE BRUTUM 19
	ADHESIVE BRUTUM 19HF
	ADHESIVE BRUTUM 19MP
	ADHESIVE POLYPLUS 165
IBM CORP	ADHESIVE IBM240
	ADHESIVE IBM314 EPOXY
	FINISH SYSTEM P213B
	INK TYPEWRITER RIBBON
ICI ADVANCED	PLASTIC VICTREX PES 4100G
ICO/RALLY CORP	TUBING FIBERGLASS SLV 1200
	TUBING HS HEATRAX 8509
IDEMITSU OIL CHEMICAL	TUBING IDEMITSU POLYCARBONATE A2500
IITRI	COATING S13 GLO THERMAL CONTROL SILICONE
ILC DOVER	BLADDER URETHANE
	COATING IMPREGNANT GLOVE POLYURETHANE
	COATING POLYURETHANE PLENUM FILM
	CONFIG COMPOSITE SHUTTLE SUIT
	FABRIC COTTON COVERALL (DRY-CLEANED 25 TIMES)
	FABRIC COTTON POCKET CWG
	FILM POLYURETHANE GLOVE BLADDER
	GLOVE CLOTH NOMEX RTV 157 GREEN
	GLOVE COMFORT NYLON/ACRYLIC
	INSULATION FOAM MOLECULON FR302 POLYURETH
	LBNPD NOMEX COVERED
	RUBBER NEOPRENE/HELMET LINER
	RUBBER POLYURETHANE RUCOTHANE 5154 WITH COTTON FLOC/RED PIGMENT
	RUBBER POLYURETHANE RUCOTHANE AX5225 WITH COTTON FLOC
	RUBBER POLYURETHANE X364
	RUBBER POLYURETHANE X364 RHOPLEX/FLOCC
	RUBBER POLYURETHANE X364 RUCOTHANE/5154
	RUBBER RUCOTHANE 5154/MS122
	RUBBER RUCOTHANE 5225/MS122
ILLBRUCK	INSULATION FOAM SONEX 1 FR POROUS ACOUSTIC MELAMINE HYPALON COATED
	INSULATION FOAM SONEX ACOUSTICAL FR
IMPCO	RESIN RC2 IMPREGNATING
IMPERIAL ADHESIVE & CHEM INC	ADHESIVE UNITAK 136
	TEFLON TFE/15% GRAPHITE
IMPERIAL CLEVITE	RUBBER HOSE LOW PRESSURE
IMPERIAL EASTMAN	HOSE HYTRON PRESSURE
	TUBING NYLON
IMPERIAL WIRE & CABLE	CABLE ELEC TFE/BEN-HAR GLUE
	WIRE ELEC TEFLON TFE
	WIRE ELEC TFE/GLASS WARP
	WIRE ELEC THERMOCOUPLE FIBERGLASS
INCREDIBLE INC	FABRIC HT-90-40 NOMEX/STN RMVR
INDEPENDENT INK	INK 41 BLACK PASTE
	INK 73X
	INK PHENOL 82L22G1 BLACK
	INK TY609 MARKING BLACK
INDUSTRIAL PLASTICS	FABRIC FARRELL FIBERGLASS
INGLA RUBBER PRODUCTS	CLAMP ST253/CUSH MOSITES 1059
INK STAMPING CO	INK MARKING ALKYD BLACK
INMONT CORP	COATING GREY ENAMEL/PRIMER
INSL-X PRODUCTS CORP	VARNISH INSULATING U86F
INSTA-FOAM PROD	INSULATION FOAM INSTA POLYURETHANE
	INSULATION FOAM POLYURETHANE KIT FP60
INSULATION MATERIAL	TUBING PTFE SHRINKABLE
INSULATION SYSTEMS	TUBING PLASTIC
	TUBING STM SILICONE NO HST
INSULECTRO	LACING TAPE AROMATIC POLYAMIDE
	LAMIN EPOXY/GLASS FR4
INTERCEL	FABRIC ZIRCONIUM TREATED WOOL
INTERCHEM CO	ADHESIVE RESIN POLYESTER 988
INTERCIRCUITS	LAMIN PRINTED WIRING BOARD /DC3140 COATED
INTERMEDCO	GLOVE LATEX SOMAMED
INTERNATIONAL ELECTRONIC	COATING INSULUBE 448 URETHANE
INTERNATIONAL HARVESTER	INSULATION FOAM POLYIMIDE 1720
	INSULATION FOAM SOLIMIDE FF201 POLYIMIDE
	INSULATION FOAM SOLIMIDE TA301 POLYIMIDE
INTERNATIONAL LATEX	FABRIC NYLON URETHANE COATED
INTERNATIONAL PAPER	CARDS CUE PAPER
INTERWOVEN INC	SOCKS COTTON TUBE
	SOCKS TUBE 90% COTTON 10%NYLON
IOWA PAINT	COATING VINYL UTC4005-30301
ISI	FABRIC NYLON 2257 NEOPRENE COATED BONDED WITH SHORE CHEMICAL UBS-N1030 ADHESIVE AND NEOPRENE COATED NYLON TAPE
ISOCHEM RESINS	ADHESIVE EP1300 A/B
	ADHESIVE EP1330 A/B
	ADHESIVE EP1350 A/B
	ADHESIVE EP1500 A/B
	ADHESIVE EP3200 A/B
	ADHESIVE EP3203 A/B
	ADHESIVE EP3230 A/B
	ADHESIVE EP3250 A/B
	ADHESIVE EP3280 A/B
	ADHESIVE EP3281 A/B
	ADHESIVE EP3285 A/B
	ADHESIVE EP3351 A/B
	ADHESIVE EP3500 A/B
	ADHESIVE EP3501 A/B
	ADHESIVE EP3641
	ADHESIVE EP3642
	ADHESIVE EP3652

MSFC-HDBK-527 REV F 9999942 0006918 6

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
ISOCHEM RESINS	ADHESIVE EP3680
	ADHESIVE EP3685
	ADHESIVE ISOCHEM BOND 1308/95A6
	MOLD COMPOUND POLYESTER MICA FILLED
	PLASTIC EP1200 H100
	PLASTIC EP1200 H130
	PLASTIC EP1200 H135
	PLASTIC EP1200 H150
	PLASTIC EP1200 H170
	PLASTIC EP1200 H180
	PLASTIC EP1200 H190
	PLASTIC EP1200 H300
	PLASTIC EP1200 H350
	PLASTIC EP1200 H400
	PLASTIC EP1200 H500
	PLASTIC EP1200 H600
	PLASTIC EP1200 H650
	PLASTIC EP1200 H670
	PLASTIC EP1205
	PLASTIC EP1210 H300
	PLASTIC EP1215 H300
	PLASTIC EP1220 H300
	PLASTIC EP1230 H300
	PLASTIC EP1240 H300
	PLASTIC EP1251 H300
	PLASTIC EP1255 H300
	PLASTIC EP1260 H300
	PLASTIC EP1400
	PLASTIC EP1400 H100
	PLASTIC EP1400 H300
	PLASTIC EP1470 H100
	PLASTIC EP1470 H300
	PLASTIC EP1505 A/B
	PLASTIC EP1525 A/B
	PLASTIC EP1548 A/B
	PLASTIC EP1561 A/B
	PLASTIC EP1562 A/B
	PLASTIC EP1800 A/B
	PLASTIC EP4200 H100
	PLASTIC EP4200 H300
	PLASTIC EP4213
	PLASTIC EP8200/AB
	PLASTIC EP8260 H190
	PLASTIC EP8260 H350
	RELEASE AGENT X-AIR 4N002
ISOCYANURATE PROD	INSULATION FOAM ISOCYANURATE MO9-58-2
	INSULATION FOAM ISOCYANURATE S16-49
	INSULATION FOAM ISOCYANURATE S17-120B
	INSULATION FOAM POLYURETHANE S17-120B
ISOTECH	INSULATION FOAM POLYURETHANE P2004
	INSULATION FOAM POLYURETHANE P2020
ITT CANNON	ADHESIVE SM8103 SILICONE
	CAPLUGS PVC EC22 CANNON 500
	CONN MPE PROTECTIVE CAPS
	CONNECTOR 40M MODIFIED
ITT CANNON	CONNECTOR DAP 280-35001-208
	CONNECTOR DAP/GLASS FILLED
	CONNECTOR ELEC DDM43W2SK52
	CONNECTOR ELEC G05D170A2BABL
	CONNECTOR ELEC M1K6-1-7-PH016
	CONNECTOR ELEC M1KM0-1-7-SH016
	CONNECTOR ELEC M24308/1-2
	CONNECTOR ELEC M24308/2-3
	CONNECTOR ELEC M24308/2-5
	CONNECTOR ELEC M24308/4-3
	CONNECTOR ELECTRICAL
	CONNECTOR ELECTRICAL 73E
	CONNECTOR ELECTRICAL PLUG
	CONNECTOR MALE-MC/ME414-0148
	CONNECTOR SEALING PLUG AL/NI
	GASKET SILICONE RUBBER
	RUBBER SILICONE SM3500-41
	RUBBER SILICONE T8296
	SEALANT SILICONE
	WIRE ELEC PD-219-21
	WIRE ELEC RAYCHEM 44 ALL GAGES
IVORY	SOAP IVORY 2OZ
J & M PRODUCTS	CABLE CLAMP ME 127-0071
	CLAMP RL5033/CUSHION L32171
	CLAMP SILICONE/CRES JM44
	TEFLON TFE RED STRIPED
J A MATTHEWS CO	INK M219 VULCAN BLACK
J L CLARK MFG	TUBING RESIN PAPER GRADE 22
J P STEVENS	FABRIC 5035/8362 BETA/SILICONE
	FABRIC BETA/SILICONE S85035
	FABRIC COTTON 2701 FR
	FABRIC COTTON FLAME RETARDANT
	FABRIC COTTON FR/POLYETHYLENE LINING
	FABRIC MODACRYLIC 6901-1151
	FABRIC STYLE 5035 FINISH 8362
	FABRIC/TAPE 581 QUARTZ (INORGANIC)
J ROYAL CO	RUBBER SILICONE O-RINGS
J-SIL	INSULATION WIRE SILICONE J-SIL39013
JAPAN AVIATION	CONNECTOR D-SUB ND101-50S-C ND101-50P-C
ELECTRONICS	CONNECTOR D-SUB ND101-9S-C/ND101-9P-C
JAPAN AVIONICS CO	CONNECTOR D-SUB DEM/DAM/DBM
	LAMIN EPOXY/GLASS CIRCUIT BOARD
JBL CORP	RUBBER SILICONE EXTREME LOW TEMPERATURE
	LOW TEMPERATURE HARDNESS SHORE "A" 65-75
JCI AMERICA	PLASTIC PES-200P
JET-LUBE	SEALANT KOPR-SHIELD
JOCKEY INTERNATIONAL	FABRIC SHORTS BOXER
	FABRIC SHORTS JOCKEY
	FABRIC TEE SHIRT
JOHN C DOLPH CO	ADHESIVE DOLPHON CA1069
	ADHESIVE DOLPHON CC1024A WITH RE2000
	ADHESIVE DOLPHON CC1024A WITH RE2005
	ADHESIVE DOLPHON CC1080
	ADHESIVE DOLPHON CC1080L
	ADHESIVE DOLPHON CC1096

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
JOHN C DOLPH CO	ADHESIVE DOLPHON CC1099
	ADHESIVE DOLPHON CC1105
	ADHESIVE DOLPHON CC1126
	ADHESIVE DOLPHON CC1129
	ADHESIVE DOLPHON CR1056-1
	ADHESIVE DOLPHON CR1056-2
	COATING POLYURETHANE ER41 CLE
	DOLPHON CB-1109
	POTTING COMPOUND CB1054 A/B EPOXY
	VARNISH SYNTHITE AC29-76
JOHNS-MANVILLE	FELT ASBESTOS
	FELT MICROFIBER TYPE E 4-6 LBS
	INSULATION AFRSI WITH DISILAZANE Z6079
	INSULATION BLANKET SILICONE/S-GLASS/Q-FELT
	INSULATION BLASTAPE II G120 MX4702
	INSULATION CEMA FIBER 111
	INSULATION CERACHROME CERAMIC INORGANIC
	INSULATION FLEX ALUMINA SILICATE
	SEALANT DUXSEAL
	TAPE BLASTAPE 2 STYLE MX4703
	TAPE MX4703-2
	THREAD QUARTZ TFE COATED
	TRANSITE
	TRANSITE PT401 COATED
JOHNSON & JOHNSON	SHAVING CREME GEL 5951 D68B
	WASH CLOTHS BABY UNSCENTED
	WAX ORIGINAL PLEDGE AEROSOL
JOMAR INTERNATIONAL	ADHESIVE JOMAR SEAL "GIMME THE GREEN STUFF"
	ADHESIVE JOMAR SEAL "THE HEAVYWEIGHT"
	ADHESIVE JOMAR SEAL "TUFFER THAN TUFF"
	ADHESIVE JOMAR SEAL W.O.G. SEAL
JONAL LABORATORIES	RUBBER VITON FLUID RESISTANT
JONATHAN TEMPLE INC	CORD FIBERGLASS/NEOPRENE
JUNKOSHA CO LTD	CABLE MULTI JUNFLON 854-048A PTFE
	TUBING FEP SPIRAL SPF61
	TUBING JUNFLON PFA
KAIKUHL RUBBER	RUBBER VITON E60C
	RUBBER VITON FLUID RESISTANT
KAL-GARD COATING & MFG	LUBE DRY KALGARD RA MOS2
KALAS MFG	WIRE ELEC PVC
KAMATICS CORP	LUBE COMPOSITE BEARING KARON
KANSAS PAINT & COLOR	COATING EPOXY POLAMIDE WITH POLYURETHANE OVERCOAT
	COATING EPOXY POLYAMIDE ON STAINLESS STEEL
KAPAK CORP	FILM KAPAK/SCOTCHPAK
KAUFMAN GLASS CO	NYLON 6/6
	PLASTIC SHEET ABS BLACK
KAYNAR CORP	FASTENER KYNAR MK 7201
	LUBE DRY
KEENE	LAMIN DECLAD 810 COPPER COATING
	TAPE GLASS/SILICONE/ADHESIVE PE2347
KELLER PRODUCTS CO	ADHESIVE X-PERT PANEL ADHESIVE
KENDALL	FABRIC NOMEX NON-WOVEN 141-329
	FABRIC POLYESTER E-1438
KENDALL	FABRIC POLYESTER NON-WOVEN
	TAPE POLYKEN 207 COTTON
	TAPE POLYKEN 224A
	TAPE POLYKEN 234A
KENYON PIECE DYEWORKS	CONFIG/SEE 20406/20579
	FABRIC NOMEX WITH ZEPEL/ARMALON/URETHANE COATED NY
	FABRIC NOMEX/ARMALON/URETHANE COATED NY
	FABRIC NOMEX/URETHANE COATED NYLON B
	FABRIC NYLON 6611 OXFORD YELLOW
	FABRIC NYLON URETHANE COATED
	FABRIC NYLON URETHANE COATED 6611
KESTER SOLDER	SOLDER KESTER SN 96
KEUFFEL & ESSER	FILM STABILENE DIAZO
	INK MARKING RADIOGRAPH 580005
	LABEL 71-6165 ALUMINIZED SIGHTING WITH PS ADHES
KIMBERLY CLARK CORP	FILM KIMFOIL
	PAPER KLEENEX TISSUE PACK
	TOWELS KAYDRY PAPER
KINETICS INC	SOUND INSUL KNB-5LR BLACK PVC
KING SEELEY THERMOS	BLANKET SURVIVAL SPACE BRAND
KINGSLEY MACHINE CO	INK MARKING K36 BLACK
	INK MARKING K480 BLUE/BLACK FOIL
	LABEL IDENTIFICATION MARKING FOIL TFE
KIRKHILL RUBBER	FABRIC GLASS/SILICONE
	FABRIC GLASS/SILICONE KSF100-2
	RUBBER COHRLASTIC R10470 SILICONE
	RUBBER EPDM NOC
	RUBBER FLUOROSILICONE 67XX
	RUBBER NBR INSULATION
	RUBBER SILICONE 950C1569
	RUBBER SILICONE 950C1569 TOX RATE STUDY
	RUBBER SILICONE CL 1A & 1B GR 80
	RUBBER SILICONE CL 2A & 2B GR 60
	RUBBER SILICONE CL 3B GR 50
	RUBBER SILICONE DURO 40
	RUBBER SILICONE DURO 70
	RUBBER SILICONE HARDNESS SHORE "A" 55-65
	RUBBER SILICONE ON AL/SILASTIC E
	RUBBER SILICONE RTV 282 ADHESIVE
	RUBBER SILICONE S899-50
	RUBBER TR3005
	SILICONE RUBBER, TR9904
	SPONGE RUBBER NEOPRENE
	SPONGE RUBBER NEOPRENE CLOSED CELL KNIT
	SPONGE RUBBER NEOPRENE OPEN CELL 2-S-198
	SPONGE RUBBER SILICONE
KITAGAWA INDUSTRIES CO	HARNESS PROTECTOR TEFLON GROMMET EDGING KG-023F
KLOPMAN MILLS	FABRIC ARAMID 3/K-GUARD 787818
	FABRIC COTTON/DACRON
	FABRIC NOMEX 7878-18 BLUE
	FABRIC NOMEX K-GUARD/ADP/KEL-F
	FABRIC NOMEX TWILL 60Z NATURAL

MSFC-HDBK-527 REV F 9999942 0006920 4

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
KLOPMAN MILLS	FABRIC NOMEX TWILL 6OZ BLACK
	FABRIC NOMEX TWILL 6OZ GOLD
	FABRIC NOMEX TWILL 6OZ RED
	LABEL NOMEX/RAYON
KOLLMORGEN CORP	LAMIN EPOXY/GLASS
KOPPERS	COATING A276/P527D
KOPPERS CO	COATING 36231 ALKYD ENAMEL
	COATING A136 EPOXY
	COATING A1716/BT1-1
	COATING ALKYD GLOSS ENAMEL 12246
	COATING ALUMINIZED ENAMEL SEE REPORT
	COATING DC 4-77 ENAMEL
	COATING ENAMEL A316/A136 EXP PRIMER
	COATING EPOXY PRIMER A136-2CP AB
	COATING EPOXY/POLYAMIDE
	COATING P527D/C527D/PRIMER
	COATING PRIMER P605-66/C152-66 BLUE
	COATING WASH PRETREATMENT
	COATING ZINC CHROMATE
	INK MARKING A423-66 BASE T252-66 CONVERTER
L & M ELECTRONICS	BOTTLE VACUUM #SL-4VBA
	BOTTLE VACUUM SERIES #2
	CABLE HARNESS 3AFT 23-15
L & M-SURCO MFG, INC	ADHESIVE L & M CERAMIC FLOOR ADHESIVE 16
	ADHESIVE L & M CERAMIC FLOOR ADHESIVE B272
	ADHESIVE L & M CERAMIC WALL TILE ADHESIVE A282
	ADHESIVE L & M MULTI-PURPOSE CERAMIC WALL AND TILE ADH TYPE 1 B-289
	ADHESIVE L-M CERAMIC FLOOR
L FRANK MARKEL & SON	RUBBER SILICONE SR200
L N P CORP	FLUOROCOMP #103
	PLASTIC EMI-X DA30
	PLASTIC EMI-X DA35
	PLASTIC EMI-X DA40
	PLASTIC EMI-X DC1008
	PLASTIC EMI-X EC1008
	PLASTIC EMI-X IC1008
	PLASTIC EMI-X MA40
	PLASTIC EMI-X OC100-10
	PLASTIC EMI-X PC100-10
	PLASTIC EMI-X PC1008
	PLASTIC EMI-X QC100-10
	PLASTIC EMI-X QC1008
	PLASTIC EMI-X RA30
	PLASTIC EMI-X RA35
	PLASTIC EMI-X RA40
	PLASTIC EMI-X RC100-10
	PLASTIC EMI-X RC100-12
	PLASTIC EMI-X RC1008
	PLASTIC EMI-X WA40
	PLASTIC EMI-X WC1008
	PLASTIC EMI-X ZC1008
	PLASTIC FLUOROMELT FPCC1004
	PLASTIC FLUOROMELT FPCF1004

MANUFACTURER	DESIGNATION
L N P CORP	PLASTIC FLUOROMELT FPCF1006
	PLASTIC FLUOROMELT FPCL4020
	PLASTIC FLUOROMELT FPCLF4024
	PLASTIC FLUOROMELT FPEC1004
	PLASTIC FLUOROMELT FPEC1006
	PLASTIC FLUOROMELT FPEEL4024
	PLASTIC FLUOROMELT FPEF1004
	PLASTIC FLUOROMELT FPEF1006
	PLASTIC FLUOROMELT FPEL4060
	PLASTIC FLUOROMELT FPFC1003
	PLASTIC FLUOROMELT FPFF1004
	PLASTIC FLUOROMELT FPFF1004M
	PLASTIC FLUOROMELT FPFL4020
	PLASTIC FLUOROMELT FPPC1003
	PLASTIC FLUOROMELT FPPCL4024
	PLASTIC FLUOROMELT FPPF1004
	PLASTIC FLUOROMELT FPPF1004M
	PLASTIC FLUOROMELT FPPL4020
	PLASTIC FLUOROMELT FPVC1003
	PLASTIC FLUOROMELT FPVCL4024
	PLASTIC FLUOROMELT FPVM2550
	PLASTIC FLUOROMELT FPVM3830
	PLASTIC FLUOROMELT FPVM3850
	PLASTIC FULTON 404
	PLASTIC LNPD1000
	PLASTIC LNPDA1004
	PLASTIC LNPKL4410
	PLASTIC LNPKL4610
	PLASTIC LNPO1000
	PLASTIC LNPOFA1004
	PLASTIC LNPOFA1008
	PLASTIC LNPP1000
	PLASTIC LNPPA 6/10
	PLASTIC LNPPA 6/6
	PLASTIC LNPPA1002
	PLASTIC LNPPA1004
	PLASTIC LNPPA6
	PLASTIC LNPR1000
	PLASTIC LNPR5000
	PLASTIC LNPRA1002
	PLASTIC LNPRA1004
	PLASTIC LNPRAL4023
	PLASTIC LNPRCL4536
	PLASTIC LNPRCL4736
	PLASTIC LNPRE5006
	PLASTIC LNPREL4536
	PLASTIC LNPREL4736LW
	PLASTIC LNPRL4610
	PLASTIC LNPRL4620
	PLASTIC LNPW1000
	PLASTIC LNPWA1004
	PLASTIC LUBRICOMP A1000
	PLASTIC LUBRICOMP AL4030
	PLASTIC LUBRICOMP AL4410
	PLASTIC LUBRICOMP B1000

MSFC-HDBK-527 REV F 9999942 0006921 6

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
L N P CORP	PLASTIC LUBRICOMP BBL4326
	PLASTIC LUBRICOMP BFL4036
	PLASTIC LUBRICOMP BFL4536
	PLASTIC LUBRICOMP BL4030
	PLASTIC LUBRICOMP BL4410
	PLASTIC LUBRICOMP BL4530
	PLASTIC LUBRICOMP C1000
	PLASTIC LUBRICOMP CL4030
	PLASTIC LUBRICOMP CL4410
	PLASTIC LUBRICOMP D1000
	PLASTIC LUBRICOMP DC1006
	PLASTIC LUBRICOMP DF1006
	PLASTIC LUBRICOMP DFL4034
	PLASTIC LUBRICOMP DFL4038
	PLASTIC LUBRICOMP DFL4536
	PLASTIC LUBRICOMP DL4010
	PLASTIC LUBRICOMP DL4040
	PLASTIC LUBRICOMP DL4530
	PLASTIC LUBRICOMP F1000
	PLASTIC LUBRICOMP FJL4036
	PLASTIC LUBRICOMP FL4040
	PLASTIC LUBRICOMP FPC1000
	PLASTIC LUBRICOMP FPC1003
	PLASTIC LUBRICOMP FPCF1004M
	PLASTIC LUBRICOMP FPCF1005
	PLASTIC LUBRICOMP FPE1000
	PLASTIC LUBRICOMP FPEC1003
	PLASTIC LUBRICOMP FPEC1006
	PLASTIC LUBRICOMP FPEF1002
	PLASTIC LUBRICOMP FPEF1003
	PLASTIC LUBRICOMP FPEF1004
	PLASTIC LUBRICOMP FPEF1004M
	PLASTIC LUBRICOMP FPEF1005
	PLASTIC LUBRICOMP FPEF1006
	PLASTIC LUBRICOMP FPEFL4035
	PLASTIC LUBRICOMP FPEL4060
	PLASTIC LUBRICOMP FPEL4210
	PLASTIC LUBRICOMP FPEL4320
	PLASTIC LUBRICOMP FPF1000
	PLASTIC LUBRICOMP FPFC1003
	PLASTIC LUBRICOMP FPFF1003M
	PLASTIC LUBRICOMP FPFF1004M
	PLASTIC LUBRICOMP FPP1000
	PLASTIC LUBRICOMP FPPC1003PC
	PLASTIC LUBRICOMP FPPF1004
	PLASTIC LUBRICOMP FPPF1004M
	PLASTIC LUBRICOMP FPPML3312
	PLASTIC LUBRICOMP FPV1000
	PLASTIC LUBRICOMP FPVC1003
	PLASTIC LUBRICOMP FPVCL4024
	PLASTIC LUBRICOMP FPVM2550
	PLASTIC LUBRICOMP FPVM3850
	PLASTIC LUBRICOMP FULTON 404D
	PLASTIC LUBRICOMP FULTON 441
	PLASTIC LUBRICOMP FULTON 441D

MANUFACTURER	DESIGNATION
L N P CORP	PLASTIC LUBRICOMP G1000
	PLASTIC LUBRICOMP GC1006
	PLASTIC LUBRICOMP GF1006
	PLASTIC LUBRICOMP GFL4022
	PLASTIC LUBRICOMP GFL4036
	PLASTIC LUBRICOMP GL4030
	PLASTIC LUBRICOMP GL4520
	PLASTIC LUBRICOMP GML4334
	PLASTIC LUBRICOMP H1000
	PLASTIC LUBRICOMP HFL4325
	PLASTIC LUBRICOMP I1000
	PLASTIC LUBRICOMP IC1006
	PLASTIC LUBRICOMP IF1006
	PLASTIC LUBRICOMP IFL4036
	PLASTIC LUBRICOMP IFL4536
	PLASTIC LUBRICOMP IL4040
	PLASTIC LUBRICOMP IL4410
	PLASTIC LUBRICOMP IL4530
	PLASTIC LUBRICOMP JL4030
	PLASTIC LUBRICOMP K1000
	PLASTIC LUBRICOMP KC1004
	PLASTIC LUBRICOMP KF1006
	PLASTIC LUBRICOMP KFL4036
	PLASTIC LUBRICOMP KFL4536
	PLASTIC LUBRICOMP KL4010
	PLASTIC LUBRICOMP KL4020
	PLASTIC LUBRICOMP KL4030
	PLASTIC LUBRICOMP KL4050
	PLASTIC LUBRICOMP KL4320
	PLASTIC LUBRICOMP KL4540
	PLASTIC LUBRICOMP KL4540D
	PLASTIC LUBRICOMP LCL4033
	PLASTIC LUBRICOMP LFL4036
	PLASTIC LUBRICOMP LL4040
	PLASTIC LUBRICOMP M1000
	PLASTIC LUBRICOMP MFL4036 HS
	PLASTIC LUBRICOMP ML4040 HS
	PLASTIC LUBRICOMP NYKON P
	PLASTIC LUBRICOMP NYKON Q
	PLASTIC LUBRICOMP NYKON R
	PLASTIC LUBRICOMP O1000
	PLASTIC LUBRICOMP OC1006
	PLASTIC LUBRICOMP OF1008
	PLASTIC LUBRICOMP OFL4326
	PLASTIC LUBRICOMP OFL4536
	PLASTIC LUBRICOMP OL4040
	PLASTIC LUBRICOMP P1000
	PLASTIC LUBRICOMP PC1006
	PLASTIC LUBRICOMP PDX4208
	PLASTIC LUBRICOMP PDX5156
	PLASTIC LUBRICOMP PF1006
	PLASTIC LUBRICOMP PFL4036
	PLASTIC LUBRICOMP PFL4536
	PLASTIC LUBRICOMP PL4030
	PLASTIC LUBRICOMP PL4040

MSFC-HDBK-527 REV F 9999942 0006922 8

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
L N P CORP	PLASTIC LUBRICOMP PL4310
	PLASTIC LUBRICOMP PL4540
	PLASTIC LUBRICOMP Q1000
	PLASTIC LUBRICOMP QC1006
	PLASTIC LUBRICOMP QF1006
	PLASTIC LUBRICOMP QFL4036
	PLASTIC LUBRICOMP QFL4536
	PLASTIC LUBRICOMP QL4040
	PLASTIC LUBRICOMP QL4410
	PLASTIC LUBRICOMP QL4540
	PLASTIC LUBRICOMP R1000
	PLASTIC LUBRICOMP RC1004
	PLASTIC LUBRICOMP RC1006
	PLASTIC LUBRICOMP RC1008
	PLASTIC LUBRICOMP RF100-10
	PLASTIC LUBRICOMP RF1002
	PLASTIC LUBRICOMP RF1004
	PLASTIC LUBRICOMP RF1006
	PLASTIC LUBRICOMP RF1008
	PLASTIC LUBRICOMP RFL4036
	PLASTIC LUBRICOMP RFL4416
	PLASTIC LUBRICOMP RFL4536
	PLASTIC LUBRICOMP RFL4616
	PLASTIC LUBRICOMP RL4010
	PLASTIC LUBRICOMP RL4040
	PLASTIC LUBRICOMP RL4040 FR
	PLASTIC LUBRICOMP RL4310
	PLASTIC LUBRICOMP RL4410
	PLASTIC LUBRICOMP RL4540
	PLASTIC LUBRICOMP RL4610
	PLASTIC LUBRICOMP RL4730
	PLASTIC LUBRICOMP S1000
	PLASTIC LUBRICOMP SFL4036
	PLASTIC LUBRICOMP SL4040
	PLASTIC LUBRICOMP SL4610
	PLASTIC LUBRICOMP T1000
	PLASTIC LUBRICOMP TF1006
	PLASTIC LUBRICOMP TFL4036
	PLASTIC LUBRICOMP TFL4536
	PLASTIC LUBRICOMP TL4030
	PLASTIC LUBRICOMP TL4410
	PLASTIC LUBRICOMP V1000
	PLASTIC LUBRICOMP VFL4036
	PLASTIC LUBRICOMP VICTREX PEEK D450HF30
	PLASTIC LUBRICOMP VICTREX PEEK D450HT15
	PLASTIC LUBRICOMP VICTREX PES 4800G
	PLASTIC LUBRICOMP VICTREX PES PDX86174
	PLASTIC LUBRICOMP VL4040
	PLASTIC LUBRICOMP VL4410
	PLASTIC LUBRICOMP VL4530
	PLASTIC LUBRICOMP W1000
	PLASTIC LUBRICOMP WC1006
	PLASTIC LUBRICOMP WF1006
	PLASTIC LUBRICOMP WFL4036
	PLASTIC LUBRICOMP WFL4536

MANUFACTURER	DESIGNATION
L N P CORP	PLASTIC LUBRICOMP WL4030
	PLASTIC LUBRICOMP WL4410
	PLASTIC LUBRICOMP WL4540
	PLASTIC LUBRICOMP X1000
	PLASTIC LUBRICOMP XC1006
	PLASTIC LUBRICOMP XF1006
	PLASTIC LUBRICOMP XL4040
	PLASTIC LUBRICOMP Y1000
	PLASTIC LUBRICOMP YF1006
	PLASTIC LUBRICOMP YFL4536
	PLASTIC LUBRICOMP YL4030
	PLASTIC LUBRICOMP YL4410
	PLASTIC LUBRICOMP YL4530
	PLASTIC LUBRICOMP Z1000
	PLASTIC LUBRICOMP ZBL4326
	PLASTIC LUBRICOMP ZF1006
	PLASTIC LUBRICOMP ZFL4036
	PLASTIC LUBRICOMP ZFL4323
	PLASTIC LUBRICOMP ZL4030
	PLASTIC LUBRICOMP ZML4334
	PLASTIC NY-KON I
	PLASTIC NY-KON P
	PLASTIC NY-KON Q
	PLASTIC NY-KON R
	PLASTIC PDX-82427
	PLASTIC PDX-82428
	PLASTIC PDX-83238
	PLASTIC PDX-83392
	PLASTIC PDX-83393
	PLASTIC PDX-84356
	PLASTIC PDX-84357
	PLASTIC PDX-84367 PEI
	PLASTIC PDX-84369 PBT
	PLASTIC PDX-84440 EVA
	PLASTIC STAT-KON AC-1003
	PLASTIC STAT-KON AC-1006
	PLASTIC STAT-KON AS-F
	PLASTIC STAT-KON AS-FE
	PLASTIC STAT-KON BLM
	PLASTIC STAT-KON D
	PLASTIC STAT-KON D-FR
	PLASTIC STAT-KON DC-1003-FR
	PLASTIC STAT-KON DC-1006
	PLASTIC STAT-KON DCF-1006 15C/15G
	PLASTIC STAT-KON DCL-4033
	PLASTIC STAT-KON DF-15
	PLASTIC STAT-KON DF-FR
	PLASTIC STAT-KON EC-1003
	PLASTIC STAT-KON EC-1006
	PLASTIC STAT-KON FE
	PLASTIC STAT-KON FP-CC-1004
	PLASTIC STAT-KON FP-E
	PLASTIC STAT-KON FP-EC-1004
	PLASTIC STAT-KON FP-P
	PLASTIC STAT-KON FP-PC-1004

MSFC-HDBK-527 REV F 9999942 0006923 T

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
L N P CORP	PLASTIC STAT-KON FP-VC-1003
	PLASTIC STAT-KON GC-1003
	PLASTIC STAT-KON GC-1006
	PLASTIC STAT-KON H
	PLASTIC STAT-KON IC-1006
	PLASTIC STAT-KON JC-1003
	PLASTIC STAT-KON JC-1006
	PLASTIC STAT-KON KC-1002
	PLASTIC STAT-KON KCL-4022
	PLASTIC STAT-KON LC-1006
	PLASTIC STAT-KON LCL-4033
	PLASTIC STAT-KON M1 HI
	PLASTIC STAT-KON M2
	PLASTIC STAT-KON ME
	PLASTIC STAT-KON MF-15
	PLASTIC STAT-KON MM3340
	PLASTIC STAT-KON OC-1003
	PLASTIC STAT-KON OC-1006
	PLASTIC STAT-KON OCL-4036
	PLASTIC STAT-KON PC-1002
	PLASTIC STAT-KON PC-1006
	PLASTIC STAT-KON PDX-84368 PC
	PLASTIC STAT-KON QC-1002
	PLASTIC STAT-KON QC-1006
	PLASTIC STAT-KON R
	PLASTIC STAT-KON RC-1002
	PLASTIC STAT-KON RC-1004
	PLASTIC STAT-KON RC-1004-FR
	PLASTIC STAT-KON RC-1006
	PLASTIC STAT-KON RC-1006-HI
	PLASTIC STAT-KON RCF-1006
	PLASTIC STAT-KON RCL-4036
	PLASTIC STAT-KON RCL-4042
	PLASTIC STAT-KON RCL-4536
	PLASTIC STAT-KON RF-15
	PLASTIC STAT-KON T
	PLASTIC STAT-KON VC-1003
	PLASTIC STAT-KON WC-1002
	PLASTIC STAT-KON WC-1006
	PLASTIC STAT-KON ZC-1003
	PLASTIC THERMOCOMP AF-1004
	PLASTIC THERMOCOMP AF-1006
	PLASTIC THERMOCOMP AF-1008
	PLASTIC THERMOCOMP BF-1004
	PLASTIC THERMOCOMP BF-1006
	PLASTIC THERMOCOMP BF-1006FR
	PLASTIC THERMOCOMP BF-1007
	PLASTIC THERMOCOMP BF-1008
	PLASTIC THERMOCOMP CF-1004
	PLASTIC THERMOCOMP CF-1006
	PLASTIC THERMOCOMP DC-1003FR
	PLASTIC THERMOCOMP DC-1006
	PLASTIC THERMOCOMP DC-1006PC
	PLASTIC THERMOCOMP DF-1004
	PLASTIC THERMOCOMP DF-1006

MANUFACTURER	DESIGNATION
L N P CORP	PLASTIC THERMOCOMP DF-1008
	PLASTIC THERMOCOMP DFA-113
	PLASTIC THERMOCOMP DFL-4036
	PLASTIC THERMOCOMP DL-4020FR
	PLASTIC THERMOCOMP DL-4030
	PLASTIC THERMOCOMP EC-1006
	PLASTIC THERMOCOMP EC-1008
	PLASTIC THERMOCOMP EF-1004
	PLASTIC THERMOCOMP EF-1006
	PLASTIC THERMOCOMP EF-1008
	PLASTIC THERMOCOMP EFL-4036
	PLASTIC THERMOCOMP FC-102CF
	PLASTIC THERMOCOMP FF-1004
	PLASTIC THERMOCOMP FF-1006
	PLASTIC THERMOCOMP FF-1008
	PLASTIC THERMOCOMP FP-EC-1004
	PLASTIC THERMOCOMP FP-PC-1003
	PLASTIC THERMOCOMP FP-VC-1003
	PLASTIC THERMOCOMP FS-100-10
	PLASTIC THERMOCOMP FULTON 441
	PLASTIC THERMOCOMP FULTON 441D
	PLASTIC THERMOCOMP GC-1006
	PLASTIC THERMOCOMP GF-1004
	PLASTIC THERMOCOMP GF-1006
	PLASTIC THERMOCOMP GF-1006FR
	PLASTIC THERMOCOMP GF-1008
	PLASTIC THERMOCOMP HF-1006
	PLASTIC THERMOCOMP IC-1006
	PLASTIC THERMOCOMP IF-100-10
	PLASTIC THERMOCOMP IF-100-12
	PLASTIC THERMOCOMP IF-1002
	PLASTIC THERMOCOMP IF-1004
	PLASTIC THERMOCOMP IF-1006
	PLASTIC THERMOCOMP IF-1008
	PLASTIC THERMOCOMP JC-1006
	PLASTIC THERMOCOMP JCL-4036
	PLASTIC THERMOCOMP JF-1006
	PLASTIC THERMOCOMP KB-1008
	PLASTIC THERMOCOMP KC-1004
	PLASTIC THERMOCOMP KF-1006
	PLASTIC THERMOCOMP KFX-1002
	PLASTIC THERMOCOMP KFX-1006
	PLASTIC THERMOCOMP KFX-1008MG
	PLASTIC THERMOCOMP MF-1002
	PLASTIC THERMOCOMP MF-1002HI
	PLASTIC THERMOCOMP MF-1004
	PLASTIC THERMOCOMP MF-1004FR
	PLASTIC THERMOCOMP MF-1004HI
	PLASTIC THERMOCOMP MF-1004HS
	PLASTIC THERMOCOMP MF-1006
	PLASTIC THERMOCOMP MF-1006HI
	PLASTIC THERMOCOMP MF-1006HS
	PLASTIC THERMOCOMP MF-1008
	PLASTIC THERMOCOMP MF-1008HI
	PLASTIC THERMOCOMP MF-1008HS

MSFC-HDBK-527 REV F 9999942 0006924 1

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
L N P CORP	PLASTIC THERMOCOMP MFX-1004HS
	PLASTIC THERMOCOMP MFX-1006HS
	PLASTIC THERMOCOMP MFX-1008HS
	PLASTIC THERMOCOMP MOS2 LUBED NYLON
	PLASTIC THERMOCOMP NF1004
	PLASTIC THERMOCOMP NF1006
	PLASTIC THERMOCOMP NF1008
	PLASTIC THERMOCOMP OC-1006
	PLASTIC THERMOCOMP OCL-4036
	PLASTIC THERMOCOMP OF-1006
	PLASTIC THERMOCOMP OF-1008
	PLASTIC THERMOCOMP OFL-4036
	PLASTIC THERMOCOMP PC-1006
	PLASTIC THERMOCOMP PDX-79738
	PLASTIC THERMOCOMP PDX-81319
	PLASTIC THERMOCOMP PF-100-10
	PLASTIC THERMOCOMP PF-100-12
	PLASTIC THERMOCOMP PF-1002
	PLASTIC THERMOCOMP PF-1002HI
	PLASTIC THERMOCOMP PF-1004
	PLASTIC THERMOCOMP PF-1004HI
	PLASTIC THERMOCOMP PF-1006
	PLASTIC THERMOCOMP PF-1006FR
	PLASTIC THERMOCOMP PF-1006HI
	PLASTIC THERMOCOMP PF-1008
	PLASTIC THERMOCOMP PF-1008HI
	PLASTIC THERMOCOMP PFL-4216
	PLASTIC THERMOCOMP PFL-4218
	PLASTIC THERMOCOMP QC-1006
	PLASTIC THERMOCOMP QF-100-10
	PLASTIC THERMOCOMP QF-100-12
	PLASTIC THERMOCOMP QF-1002
	PLASTIC THERMOCOMP QF-1004
	PLASTIC THERMOCOMP QF-1006
	PLASTIC THERMOCOMP QF-1006FR
	PLASTIC THERMOCOMP QF-1008
	PLASTIC THERMOCOMP R1000 FR
	PLASTIC THERMOCOMP R1000 FR HS
	PLASTIC THERMOCOMP RC-1002
	PLASTIC THERMOCOMP RC-1004
	PLASTIC THERMOCOMP RC-1006
	PLASTIC THERMOCOMP RC-1006HI
	PLASTIC THERMOCOMP RC-1006PC
	PLASTIC THERMOCOMP RC-1008
	PLASTIC THERMOCOMP RCL-4036
	PLASTIC THERMOCOMP RCL-4536
	PLASTIC THERMOCOMP RF-100-10
	PLASTIC THERMOCOMP RF-100-12
	PLASTIC THERMOCOMP RF-1002
	PLASTIC THERMOCOMP RF-1002HI
	PLASTIC THERMOCOMP RF-1004
	PLASTIC THERMOCOMP RF-1004FR
	PLASTIC THERMOCOMP RF-1004FR HS
	PLASTIC THERMOCOMP RF-1004HI
	PLASTIC THERMOCOMP RF-1006
L N P CORP	PLASTIC THERMOCOMP RF-1006FR
	PLASTIC THERMOCOMP RF-1006HI
	PLASTIC THERMOCOMP RF-1008
	PLASTIC THERMOCOMP RF-1008HI
	PLASTIC THERMOCOMP RFL-4216
	PLASTIC THERMOCOMP RFL-4218
	PLASTIC THERMOCOMP RL-4310
	PLASTIC THERMOCOMP SF-1006
	PLASTIC THERMOCOMP STAT-KON D
	PLASTIC THERMOCOMP STYPRENIC
	PLASTIC THERMOCOMP UF-1006
	PLASTIC THERMOCOMP UNFORTIFIED NYLON 11
	PLASTIC THERMOCOMP UNFORTIFIED NYLON 12
	PLASTIC THERMOCOMP UNFORTIFIED NYLON 6
	PLASTIC THERMOCOMP UNFORTIFIED NYLON 6/10
	PLASTIC THERMOCOMP UNFORTIFIED NYLON 6/12
	PLASTIC THERMOCOMP UNFORTIFIED NYLON 6/6
	PLASTIC THERMOCOMP VC-1006
	PLASTIC THERMOCOMP WC-1006
	PLASTIC THERMOCOMP WF-1002
	PLASTIC THERMOCOMP WF-1002HI
	PLASTIC THERMOCOMP WF-1004
	PLASTIC THERMOCOMP WF-1004HI
	PLASTIC THERMOCOMP WF-1006
	PLASTIC THERMOCOMP WF-1006FR
	PLASTIC THERMOCOMP WF-1006HI
	PLASTIC THERMOCOMP WF-1008
	PLASTIC THERMOCOMP WF-1008HI
	PLASTIC THERMOCOMP XC-1006
	PLASTIC THERMOCOMP XF-1004
	PLASTIC THERMOCOMP XF-1006
	PLASTIC THERMOCOMP XFL-4036
	PLASTIC THERMOCOMP ZF-1004
	PLASTIC THERMOCOMP ZF-1006
	PLASTIC THERMOCOMP ZF-1008
	PLASTIC VERTON RF-700-10
	PLASTIC VERTON RF-700-1EM
	PLASTIC VERTON RF-7003FR
	PLASTIC VERTON RF-7006
	PLASTIC VERTON RF-7006EM
	PLASTIC VERTON RF-7006FR
	PLASTIC VICTREX PEEK 450CA30
	PLASTIC VICTREX PEEK 450G
	PLASTIC VICTREX PEEK 450GL30
	PLASTIC VICTREX PEEK D150CA30
	PLASTIC VICTREX PEEK D150GL30
	PLASTIC VICTREX PES 4100G
	PLASTIC VICTREX PES 4101GL20
	PLASTIC VICTREX PES 410GL30
	PLASTIC VICTREX PES D4800HF30
	PLASTIC VICTREX PES D4800HL15
L TRAVIS TEXTILES	FABRIC NOMEX 98379
	FABRIC NOMEX RED 5-502 FP/WP
	FABRIC NOMEX TWILL 98379 6 OZ.
	FABRIC NOMEX/ARMALON BACKING

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
L TRAVIS TEXTILES	FABRIC NOMEX/ARMALON/URETHANE COATED NY
	FABRIC NOMEX/URETHANE COATED NYLON B
	FABRIC NYLON CHIFFON
L'AIR LIQUIDE	INSULATION FOAM CELLULAIRE H920A PVC
LABARGE	WIRE ELEC FEP/POLYIMIDE TAPE
LACROIX U KRESS	WIRE ELEC LACKDRAHTW180HW11
LAKE CHEMICAL CO	COATING LACQUER STICK BLACK
	SEALANT OXY-TITE WITH TEFLON THREAD
LAKE CITY INDUSTRIAL	TAPE TEFLON
	TAPE TEFLON PTFE ANTISEIZE
	TAPE TEFLON THREAD
	TAPE THREAD SEAL PTFE AQM
LAMART CORP	TAPE SCOTCH 861 ALUMINUM WITH PRESSURE SENSITIVE ADHESIVE
	TUBING TYGON/L-T-80 TAPE WRAP
LAMONS METAL GASKET	SEALANT SPIRASEAL METAL/TFE
LANGENTHAL	FABRIC ZIRCONIUM TREATED WOOL
LATEX PRODUCTS	RUBBER CHLOROPRENE CPD 2408A
LAUREL INDUSTRIES	FABRIC 6009-1-1
LEAR SIEGLER	ADHESIVE A5900 PHENOLIC THERMOSET
	FABROID T1 GLASS/TEFLON 50/50
	LINER FIBRILOID NOMEX/TFE
	SEALANT 905 EPOXY
LEFCO WELD	ADHESIVE BONDING LM52 T46
LEFFINGWELL CHEM CO	ADHESIVE LEFKOWELD 109/LM52 EPOXY
	ADHESIVE LEFKOWELD 157
	ADHESIVE LEFKOWELD 209
	ADHESIVE LEFKOWELD 211
	ADHESIVE LEFKOWELD 218-5
	ADHESIVE LEFKOWELD 221
	ADHESIVE LEFKOWELD 46/52 EPOXY
LETRASET USA INC	LABEL LETRALINE #11
LIBERTY FABRICS INC	FABRIC SPANDEX 90221/FIN 1635
LIFE LIMITED	RUBBER EPMD264
LION BROTHERS CO	EMBLEM CLOTH NASA
LITHGOW LABORATORY	GLOVE HANDLING ANIMAL 645
LITTON INDUSTRIES	PAPER FITCHBURG TIME MARK 30
LOCKHEED	COATING ENAMEL C144
	COATING LAC37-722A TY2/TT-P1757
	COATING SILICONE GLASS/TETRABRN FIL
	INSULATION FOAM POLYURETHANE LAC28-4102
	INSULATION S102/SIC/AB312 GLZ (INORGANIC)
	MULTI-LAYERED INSULATION AL/AU COATED/ VELCRO/ACRYLIC
	MULTI-LAYERED INSULATION PLASTIC/VELCRO/AU COATED
	POTTING COMPOUND DOLPHS CB1078/HARDNER
	TILE SILICA LI0036/OVERCOATED
	TILE SILICA LI0050/OVERCOATED
	WIRE ELEC WITH POLYIMIDE INSULATION
LOCKWOOD	TAPE TEFLON/ACRYLIC 5396
LOCTITE CORP	ADHESIVE ASSURE ELECTRICAL TYPE RETAINER
	ADHESIVE ASSURE ELECTRICAL TYPE THREADLOCKER
LOCTITE CORP	ADHESIVE ASSURE SURFACE CURING THREADLOCKER
	ADHESIVE CYANOACRYLATE
	ADHESIVE DEPEND 330
	ADHESIVE IMPRUV 349
	ADHESIVE IMPRUV 365
	ADHESIVE IMPRUV 366
	ADHESIVE IMPRUV GENERAL PURPOSE ADHESIVE
	ADHESIVE IMPRUV SEALANT/ADHESIVE
	ADHESIVE LOCTITE 221
	ADHESIVE LOCTITE 222-41
	ADHESIVE LOCTITE 222/GR-T PRIMER
	ADHESIVE LOCTITE 241
	ADHESIVE LOCTITE 242
	ADHESIVE LOCTITE 262
	ADHESIVE LOCTITE 270
	ADHESIVE LOCTITE 271 THREADLOCK
	ADHESIVE LOCTITE 277
	ADHESIVE LOCTITE 290
	ADHESIVE LOCTITE 306 ACRYLIC
	ADHESIVE LOCTITE 324
	ADHESIVE LOCTITE 326
	ADHESIVE LOCTITE 416 CYANOACRYLIC
	ADHESIVE LOCTITE 493
	ADHESIVE LOCTITE 495
	ADHESIVE LOCTITE 504
	ADHESIVE LOCTITE 515
	ADHESIVE LOCTITE 601 EPOXY
	ADHESIVE LOCTITE 609
	ADHESIVE LOCTITE 620
	ADHESIVE LOCTITE 635
	ADHESIVE LOCTITE 680
	ADHESIVE LOCTITE 69 HYDRAULIC SEALANT
	ADHESIVE LOCTITE 75
	ADHESIVE LOCTITE 80092 SUPERGLUE
	ADHESIVE LOCTITE 80414 LOCKNUTS
	ADHESIVE LOCTITE 80418
	ADHESIVE LOCTITE 80426
	ADHESIVE LOCTITE 80477
	ADHESIVE LOCTITE A
	ADHESIVE LOCTITE BLACK MAX
	ADHESIVE LOCTITE E/LOCTITE T PRIMER
	ADHESIVE LOCTITE HV
	ADHESIVE LOCTITE LO555
	ADHESIVE LOCTITE QUICK-SET ADHESIVE 404
	ADHESIVE LOCTITE SCREWLOCK/T PRIMER
	ADHESIVE LOCTITE ULTRA PERFORMANCE TAX PAK
	ADHESIVE OUTPUT 315
	ADHESIVE OUTPUT 383
	ADHESIVE OUTPUT 384
	ADHESIVE OUTPUT THERMAL CONDUCTIVE ADHESIVE
	ADHESIVE OUTPUT THERMAL CONDUCTIVE
	ADHESIVE REPAIRABLE
	ADHESIVE RAILSAFE ENGINE SEAL 12336

MSFC-HDBK-527 REV F 9999942 0006926 5

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
LOCTITE CORP	ADHESIVE SPEEDBONDER 324
	ADHESIVE SPEEDBONDER 324/CA707
	ADHESIVE SPEEDBONDER 325
	ADHESIVE SPEEDBONDER 326
	ADHESIVE SUPERBONDER 409
	ADHESIVE SUPERBONDER 414
	ADHESIVE SUPERBONDER 415
	ADHESIVE SUPERBONDER 420
	ADHESIVE SUPERBONDER 422
	ADHESIVE SUPERBONDER 430
	ADHESIVE SUPERBONDER 496 ACRYLIC
	ADHESIVE SUPERBONDER 498
	ADHESIVE SUPERBONDER 499
	ADHESIVE TAKPAK
	ADHESIVE THREADLOCKER 222
	ADHESIVE THREADLOCKER 242
	ADHESIVE THREADLOCKER 290
	ADHESIVE ULTRAVIOLET 352
	ADHESIVE ULTRAVIOLET 353
	ADHESIVE ULTRAVIOLET 354
	COATING PRIMER LOCTITE GR-T
LORD CORP	ADHESIVE CHEMLOK
	ADHESIVE CHEMLOK 2
	ADHESIVE CHEMLOK 205 PRIMER WITH CHEMLOK 220 TOPCOAT
	ADHESIVE CHEMLOK 233
	ADHESIVE CHEMLOK 234
	ADHESIVE CHEMLOK 234B
	ADHESIVE CHEMLOK 235
	ADHESIVE CHEMLOK 236A
	ADHESIVE CHEMLOK 238
	ADHESIVE CHEMLOK 246
	ADHESIVE CHEMLOK 250
	ADHESIVE CHEMLOK 252
	ADHESIVE CHEMLOK 253
	ADHESIVE CHEMLOK 304
	ADHESIVE CHEMLOK 402
	ADHESIVE CHEMLOK 607
	ADHESIVE CHEMLOK 608
	ADHESIVE CHEMLOK 810
	ADHESIVE CHEMLOK AP131
	ADHESIVE CHEMLOK BN
	ADHESIVE CHEMLOK FR
	ADHESIVE CHEMLOK G
	ADHESIVE CHEMLOK GM
	ADHESIVE CHEMLOK LR
	ADHESIVE CHEMLOK M
	ADHESIVE CHEMLOK P
	ADHESIVE CHEMLOK R
	ADHESIVE FUSOR EPOXY ADHESIVES
	ADHESIVE PRIMER CHEMLOK 205 RUBBER-TO-METAL
	ADHESIVE TYPLY 3
	ADHESIVE TYRITE 7500
	ADHESIVE TYRITE 7602

MANUFACTURER	DESIGNATION
LORD CORP	ADHESIVE TYRITE URETHANE
	ADHESIVE VERSILOK 101
	ADHESIVE VERSILOK 201
	ADHESIVE VERSILOK 202
	ADHESIVE VERSILOK 204
	ADHESIVE VERSILOK 506
	ADHESIVE VERSILOK 510
	ADHESIVE VERSILOK 513
	ADHESIVE VERSILOK 516
	ADHESIVE VERSILOK 521
	ADHESIVE VERSILOK 528 ACRYLIC
	ADHESIVE VERSILOK 551
	ADHESIVE VERSILOK 560
	ADHESIVE VERSILOK ACRYLIC
	COATING 023-GW-3/CHEMGLAZE A276 P
	COATING 44-GN-11/CHEMGLAZE A276
	COATING A276 WITH PGEA/515700/910704
	COATING CHEMGLAZE 9922 A/B
	COATING CHEMGLAZE 9924 A/B
	COATING CHEMGLAZE A170
	COATING CHEMGLAZE A276/02-GN-40 PRIMER
	COATING CHEMGLAZE A276/9924 PRIMER
	COATING CHEMGLAZE A276/KOROPON
	COATING CHEMGLAZE A276/PYROLAC 123
	COATING CHEMGLAZE A471 POLYURETHANE GRAY
	COATING CHEMGLAZE A571 RED
	COATING CHEMGLAZE A571 RED/9924
	COATING CHEMGLAZE A671 LIGHT GREEN
	COATING CHEMGLAZE A871 ORANGE
	COATING CHEMGLAZE A971 YELLOW
	COATING CHEMGLAZE H322/LESONAL PRIMER
	COATING CHEMGLAZE II A276
	COATING CHEMGLAZE II A276/9922 PRIMER
	COATING CHEMGLAZE L300
	COATING CHEMGLAZE L300/PYROLAC 123
	COATING CHEMGLAZE V021/9992
	COATING CHEMGLAZE V021/9995
	COATING CHEMGLAZE V021/XYLENE
	COATING CHEMGLAZE Z202 POLYURETHANE
	COATING CHEMGLAZE Z302
	COATING CHEMGLAZE Z302/02-GN-40PRIMER
	COATING CHEMGLAZE Z302/9922 PRIMER
	COATING CHEMGLAZE Z302/9924 PRIMER
	COATING CHEMGLAZE Z306
	COATING CHEMGLAZE Z306/02-GN-40 PRIMER
	COATING CHEMGLAZE Z306/9922 PRIMER
	COATING CHEMGLAZE Z306/9924
	COATING CHEMGLAZE Z306/AP131
	COATING CHEMGLAZE Z306/PYROLAC 123
	COATING CHEMGLAZE Z651 POLYURETHANE 9924
	COATING CHEMGLAZE Z752 POLYURETHANE 9924
	COATING CHEMGLAZE Z853/9986
	COATING EPOXY 463-12-8/4593-30
	COATING EPOXY 463-12-8/A276
	COATING POLYAMIDE WITH CHEMGLAZE Z306

MSFC-HDBK-527 REV F 9999942 0006927 7

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
LORD CORP	COATING PRIMER/CHEMGLAZE A276
	COATING Z205 SERIES
	COMPOSITE GLASS/AL/934 RESIN
	FILM KAPTON/CHEMGLAZE/BETA 107
	FILM TUFTANE T310 POLYURETHANE
	PLASTIC CHEMLOK 210
	PLASTIC CHEMLOK 218
	PLASTIC ES6040
	PLASTIC ES6060
	PLASTIC ES6071
	PLASTIC ES6072
	PLASTIC ES6360
	PLASTIC ES6461
	PLASTIC ES6477
	PLASTIC ES666
	PLASTIC FS8160
	PLASTIC FS8273
	PLASTIC FS8273-70
	PLASTIC FS8476
	PLASTIC FS8477
	PLASTIC FS8490
	PLASTIC FS8575
	RUBBER FLUOROSILICONE
	RUBBER FLUOROSILICONE NE4240
	RUBBER FLUOROSILICONE NE6072
	RUBBER FLUOROSILICONE NE7075
	RUBBER RTV 577/T-12/SS4415/A276
	RUBBER SILICONE BTR
	RUBBER SILICONE HT 2-80 SHOCK ISOLATOR
	RUBBER SILICONE NE6070
	RUBBER SILICONE NE6071/6071
	RUBBER SILICONE NE687B/5687
	RUBBER VITON NE8477
LORD KINEMATICS	RUBBER FLUOROSILICONE
LOUIS MELIND CO	INK JUSTRITE INDELIBLE
LTV AEROSPACE CORP	CARBON/GRAPHITE BONDED
	INSULATION REIN CARBON/CARBON
	LAMIN CARBON/CARBON REINFORCED
	LAMIN EPOXY/GLASS
LUBECO	LUBE DRY LUBECO 905 FILM
	LUBE DRY PHENOLIC BINDER N350A
LUBRI-KOTE CO INC	LUBE GREASE MOLYCOTE C40 CHAIN
LUDLOW CORP	RUBBER EPR MARVEL SEAL 1312
LUNAR PRODUCTS INC	INSULATION FOAM LUNAR F20 A/B EPOXY
M & T CHEMICALS	ADHESIVE EPIBOND 1210/9615A EPOXY
	ADHESIVE EPIBOND 1210A/C1210B
	ADHESIVE EPON 815 WITH EPOCAST HN951
	ADHESIVE EPON 828/EPOCAST HN951
	ADHESIVE URALANE 5753 POLYURETHANE
	COATING URALANE 5753/CIRCUIT BRD
M A BRUDER & SONS	COATING PLYTILE R294-151B EPOXY
M I T CHEMICAL	VESTIBULAR EXPERIMENT BRS
	VESTIBULAR EXPERIMENT DOME STOWAGE
	VESTIBULAR EXPERIMENT MICROCOMPUTER
	VESTIBULAR EXPERIMENT MIDDECK TRAY

MANUFACTURER	DESIGNATION
M T I	INSULATION FOAM POLYURETHANE FR
M T I CHEMICAL	INSULATION FOAM CPR1061 WITH ALBI COTE COATING
MAAS & WALDSTEIN	COATING DURACHEM 13905 EPOXY
	COATING DURACHEM 13905/DURACH 415
MAC DERMID INC	COATING MACUMASK 9446 EPOXY
MAGID CORP	SHOE SPRAY BLACK 317
MAGNA CTNG & CHEM	COATING LAMINAR X500 POLYURETHANE
	COATING TYSEAL 22W73 WHITE
MAGNET TECHNOLOGY	WIRE MAGNET P/N 1600E-056B-013
MAGNETICS	MOTOR P/N47A232920A S/N02
MALCO	CONNECTOR ELECTRICAL
MANCO INC	TAPE ALL WEATHER CW3
	TAPE DOUBLE STICKY BACK DVF1
	TAPE MANCO FIREGUARD FRD60
	TAPE POLYETHYLENE CW3
MAR-KING	INK MARKING SPECIAL 13
MARIO PAPA & SONS	GLOVE GS/FRP-2
MARKEL CORP	TAPE FLEXITE TGL BLUE ADHESIVE
	TUBING HYGRADE SR398 HA1
	TUBING HYGRADE SR398 HB1
MARKEM	INK 8447 BLACK
	INK FRS MARKING 7224
	INK MARKEM 6887 BLACK AND 112XD THINNER
	INK MARKEM 7132H
	INK MARKEM 7254 P/K BLACK
	INK MARKEM 7907 SILK SCREEN
	INK MARKEM 8855 WHITE
	INK MARKING FRS6811 BLACK
	LABEL IDENTIFICATION MYLAR/ALUMINUM ST66D28-1
MARKING METHODS	CLEANER FORMULA APC
	MARKER ELECTROLYTE MSC4
MARLIN MFG CO	CONNECTOR SILICONE
MARLING & EVANS	FABRIC NOMEX 863 TWILL
	FABRIC NOMEX 863/3 TWILL 2X2
MARLOW INDUSTRIES	ADHESIVE 3977-01 THERMAL EPOXY
MARSH STENCIL	INK STENCIL BLACK
MARSHALL	CONNECTOR MS3456L20-15PW
MARSTON BENTLEY INC	LUBE GREASE HYLOMAR PL32
	MOLDING COMPOUND HYLOMAR PL32L-25
MARTIN MARIETTA	ABLATOR SLA 561
	ADHESIVE EPON 828/DTA 7500 GLASS
	ADHESIVE SILICONE GX6300
	CHEMPOL/BETA CLOTH/113-300
	CORK P50/COATING FRL-3
	ELECTRICAL ASSEMBLY
	INSULATION BLANKET AU/AL COATED
	INSULATION BLANKET AU/AU COATED POLYIMIDE
	INSULATION FOAM BX250 FRL COATED
	INSULATION FOAM CHEMPOL/SOLITHANE 113/300
	INSULATION FOAM CPR488/FRL3 TY2 COATED
	INSULATION FOAM CPR488/TANCO 9708 COATED
	INSULATION FOAM CPR50
	INSULATION FOAM CPR50A

MSFC-HDBK-527 REV F 9999942 0006928 9

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
MARTIN MARIETTA	INSULATION FOAM NCFI 22 65 MACHINED
	INSULATION FOAM NCFI 22 65 NET SPRAY
	INSULATION FOAM NCFI 22 65/FRL3 TY1 COATED
	INSULATION FOAM NCFI 25 13
	INSULATION FOAM NCFI 6A POLYISOCYANURATE
	INSULATION FOAM NCFI 7A POLYISOCYANURATE
	INSULATION FOAM PDL4034-2.5/ SEALED WITH DAPCOSEAL 2030
	INSULATION FOAM PDL4034/COATED WITH FRL
	INSULATION FOAM PDL61
	INSULATION FOAM PDL62
	INSULATION FOAM POLYISOCYANURATE FSC17A
	INSULATION FOAM POLYSTYRENE/FR LATEX COATED
	INSULATION FOAM TU28 URETHANE
	INSULATION FOAM TU32 URETHANE
	INSULATION FOAM TX39 URETHANE
	INSULATION FOAM TX43 URETHANE
	MULTI-LAYERED INSULATION AL/KAPTON/DACRON/NOMEX/MYLAR
	PRESSURE VESSEL COMPOSITE
	RUBBER SILICONE/ALUMINUM/DC282
	WIRE ELEC VARGLASS SLEEVE 20AWG
MARTIN PROCESSING	FILM METPOLY 100
	FILM POLYESTER ALUMINIZED
MASTER BOND	ADHESIVE BLACK MAGIC
	ADHESIVE CHERABOND 18
	ADHESIVE EP11C
	ADHESIVE EP12
	ADHESIVE EP13
	ADHESIVE EP21
	ADHESIVE EP21AO
	ADHESIVE EP21CLV
	ADHESIVE EP21D
	ADHESIVE EP21HV
	ADHESIVE EP21LP
	ADHESIVE EP21LV
	ADHESIVE EP21N
	ADHESIVE EP22
	ADHESIVE EP23
	ADHESIVE EP24
	ADHESIVE EP25
	ADHESIVE EP26
	ADHESIVE EP28
	ADHESIVE EP28M
	ADHESIVE EP3
	ADHESIVE EP30
	ADHESIVE EP30C
	ADHESIVE EP30D7
	ADHESIVE EP30DP4X2
	ADHESIVE EP30DP8
	ADHESIVE EP30DP8LV
	ADHESIVE EP30HT
	ADHESIVE EP30M1
	ADHESIVE EP30S1

MANUFACTURER	DESIGNATION
MASTER BOND	ADHESIVE EP33
	ADHESIVE EP33CLV
	ADHESIVE EP33LV
	ADHESIVE EP34
	ADHESIVE EP34LV
	ADHESIVE EP35
	ADHESIVE EP35CLV
	ADHESIVE EP3AO
	ADHESIVE EP3HTFLM4
	ADHESIVE EP3HTND
	ADHESIVE EP3T
	ADHESIVE EP4
	ADHESIVE EP45
	ADHESIVE EP45N
	ADHESIVE EP5
	ADHESIVE EP51
	ADHESIVE EP51FL
	ADHESIVE EP51HT
	ADHESIVE EP51M
	ADHESIVE EP51T
	ADHESIVE EP62
	ADHESIVE EP62M
	ADHESIVE EP72
	ADHESIVE EP72AO
	ADHESIVE EP72M3
	ADHESIVE EP73
	ADHESIVE EP74
	ADHESIVE EP75
	ADHESIVE EP76
	ADHESIVE EP76M
	ADHESIVE EP76M1
	ADHESIVE EP76M1A
	ADHESIVE EP76M1R
	ADHESIVE EP76MF
	ADHESIVE EP76MHP
	ADHESIVE EP76MHT
	ADHESIVE EP76MHTHP
	ADHESIVE EP77
	ADHESIVE EP77M
	ADHESIVE EP77M1
	ADHESIVE EP77M1HP
	ADHESIVE EP77MF
	ADHESIVE EP8
	ADHESIVE EP9
	ADHESIVE MB302
	ADHESIVE MB303
	ADHESIVE SUPREME 10
	ADHESIVE SUPREME 10G
	ADHESIVE SUPREME 10HT
	ADHESIVE SUPREME 10HT N
	ADHESIVE SUPREME 10HT NHP
	ADHESIVE SUPREME 10S1
	ADHESIVE SUPREME 10TI
	ADHESIVE SUPREME 11
	ADHESIVE SUPREME 11HT

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
MASTER BOND	ADHESIVE SUPREME 3HT
	ADHESIVE SUPREME 3T
	ADHESIVE UV5PSA
MASTER BRONZE	COATING BROMA 101 CLEAR ACRYLIC
MATAC	ID PLATE PHOTO/MACBOND 1B1160
MATHISON-COLEMAN BEL	LITHIUM-STEARATE
MATRIX SCIENCE CORP	CONNECTOR CONTACT 7219
	CONNECTOR ELECT SILICONE RUBBER/CERAMIC
MAX FACTOR	EYE SHADOW PENCIL MAXI-SOFT
MAY HOSIERY MILLS	FABRIC COTTON STYLE 3715 COMBD
MAYBELLINE CO	EYE SHADOW CREME-SIL FROSTBLUE
MCB REAGENTS	PAPER COLORPHAST PH #9582
MCCAMPBELL	FABRIC SUPERTWILL 48 COTTON
MCCORDI CORP	FILM POLYESTER ALUMINIZED
MCDANIEL REFRACTORY	INSULATION POWDER S102/AL203 INORGANIC
MCDONNELL DOUGLAS	COMPOSITE VITON B50/DACRON
	COMPOSITE VITON B50/NOMEX 426
	FABRIC BETA GLASS/TFE NOC
	FABRIC HT-337 NOMEX
	INSULATION AL FOIL ON BETA CLOTH
	INSULATION BLANKET KAPTON/DACRON/NOMEX
	LAMIN EPOXY/GLASS AEROLAM 110
	LAMIN KEVLAR 49/LY8061 EPOXY
	LAMIN THORNEL 300/934 GRAPHITE/EPOXY
	LAMIN VITON B50/KEVLAR 49/181
	MULTI-LAYERED INSULATION GOLDIZED KAPTON/
	DACRON MESH/NOMEX
	RUBBER ALLOY L065-72A
	RUBBER VITON B50
	RUBBER VITON MDAC 18210-16
MCGHAN NUSIL	ADHESIVE CV1142
	ADHESIVE CV1143
	ADHESIVE CV12570
	ADHESIVE CV2564
	ADHESIVE CV2568
	LUBE GREASE SILICONE G9042
	LUBE GREASE SILICONE G9052
	RUBBER SILICONE CV1144-0
	RUBBER SILICONE CV2500
	RUBBER SILICONE CV2942
	RUBBER SILICONE RTV 510
	RUBBER SILICONE RTV R1500
	RUBBER SILICONE RTV R2500
	RUBBER SILICONE RTV R2501
	RUBBER SILICONE RTV R2510
	RUBBER SILICONE RTV R2520
	RUBBER SILICONE RTV R2566
	RUBBER SILICONE RTV R2567
MCGILL	LAMIN GILLFLOOR 5007A BALSA/GLASS
MCMASTER CARR	COATING PLASTIDIP 9560T12
	CORD BUNGEE 3862T17
	DUCT SILICONE IMPREG 5276K22
MDAC-WD	COMPOSITE VITON B50/NOMEX 426
MECHANICAL TECHNOLOGY INC	FIBER OPTICS SENSOR PROBE

MANUFACTURER	DESIGNATION
MEGATECH	COATING 856-204/855-225/850-204
MEMOREX	TAPE CASSETTE MEMOREX 120
MENARDI-SOUTHERN	SCREEN NYLON MESH
MENASCO	GREASE HYDROCARBON
MENNEN CO	DEODORANT SPEED STICK
MEPCO	COATING MEPCO FLEX
	COATING MEPCO FR14 CONFORMAL
MERECO	ADHESIVE MERECO "GDO"
	ADHESIVE MERECO 302
	ADHESIVE MERECO 3446
	ADHESIVE MERECO 3808
	ADHESIVE MERECO CN773 WITH 16C
	ADHESIVE MERECO CN773 WITH 16E
	ADHESIVE MERECO CN934
	ADHESIVE MERECO CN967
	ADHESIVE MERECO METASIL 5002
	ADHESIVE MERECO METASIL 5004
	ADHESIVE MERECO METASIL 5008
	ADHESIVE MERECO METASIL RTV 5005
	ADHESIVE MERECO METASIL XL152
	ADHESIVE MERECO SCN568
	ADHESIVE MERECO SN631
	ADHESIVE MERECO SN632
	ADHESIVE MERECO SN781
	ADHESIVE MERECO XL225
	ADHESIVE MERECO XL294
	ADHESIVE MERECO XL295
	ADHESIVE MERECO XL330
	ADHESIVE MERECO XL342
	ADHESIVE MERECO XL354
	ADHESIVE MERECO XL373
	ADHESIVE MERECO XL389
	ADHESIVE MERECO XL389T
	ADHESIVE MERECO XLM557
	ADHESIVE MERECO XLN420/CATALYST 16E
	ADHESIVE MERECO XLN420/CATALYST XL380
	ADHESIVE MERECO XLN420/CATALYST XLN474
	ADHESIVE MERECO XLN425
	ADHESIVE MERECO XLN442
	ADHESIVE MERECO XLN449
	ADHESIVE MERECO XLN455
	ADHESIVE MERECO XLN470
	ADHESIVE MERECO XLN490
	ADHESIVE MERECO XLN589
	ADHESIVE METACAST 1201
	ADHESIVE METACAST 5448 WITH #10
	ADHESIVE METACAST 5448 WITH 16E
	ADHESIVE METACAST 5448 WITH 43
	ADHESIVE METADUCT 1201 CN611
	ADHESIVE METADUCT 1202
	ADHESIVE METADUCT 1204
	ADHESIVE METADUCT 1206
	ADHESIVE METADUCT 1206 SG3
	ADHESIVE METADUCT 1206 SG4
	ADHESIVE METADUCT 1212

MSFC-HDBK-527 REV F 9999942 0006930 7

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
MERECO	ADHESIVE METADUCT 1216 SERIES
	ADHESIVE METADUCT 1216-1
	ADHESIVE METADUCT 1216-2
	ADHESIVE METADUCT 1225 SN736
	ADHESIVE METADUCT 1225 SN742
	ADHESIVE METADUCT 1225 XL245
	ADHESIVE METADUCT XL126
	ADHESIVE METADUCT XLN583 MOD 1
	ADHESIVE METAGRIP 321
	ADHESIVE METALINK 361
	ADHESIVE METREGRIP 302
	ADHESIVE METREGRIP 303
	ADHESIVE METREGRIP 303MV
	ADHESIVE METREGRIP 303VLV
	ADHESIVE METREGRIP 30LV
	ADHESIVE METREGRIP 312
	ADHESIVE METREGRIP 315
	ADHESIVE METREGRIP 321
	ADHESIVE METREGRIP 3446
	ADHESIVE METREGRIP 355
	ADHESIVE METREGRIP 385-1
	ADHESIVE METREGRIP 385-2
	ADHESIVE METRESET 3661
	ADHESIVE METRESET 3662
	ADHESIVE RAPIDSET 51QST
	ADHESIVE RAPIDSET 52SST
	ADHESIVE RAPIDSET 53HRT
	ADHESIVE RAPIDSET SERIES 2
	ADHESIVE RAPIDSET SERIES 3
	ADHESIVE RAPIDSET SERIES VISCA
	CYANOACRYLATE ADH
	ADHESIVE XL279
MERLE NORMAN	EYE SHADOW LT BLUE
METAL CRAFT	LABEL BAR CODE ACRYLIC
METALPHOTO CORP	LABEL METALPHOTO
	LABEL ULTRACOLOR 00093 KHAKI
	LABEL ULTRACOLOR 17210 BLACK
	LABEL ULTRACOLOR 17214 BROWN
	LABEL ULTRACOLOR 17215 PURPLE
	LABEL ULTRACOLOR 17218 GREEN
	LABEL ULTRACOLOR 17219 YELLOW
	LABEL ULTRACOLOR 17220 ORANGE
METALPLAST INC	POTTING COMPOUND 1MPCO RC2 POLYESTER
METEX	COATING XECOTE
	COATING XECOTE/OCF4190B WITH F017A
	COATING XECOTE/X389-7 TFE BETA
	GASKET POLASHEET SILICONE/MONEL
	GASKET SILICONE/MONEL
	RUBBER SILICONE WITH WIRE MESH
	TUBING FERREX 01-0504 SILICONE
METRON	INK MARKING RED
METRON OPTICS	INK MARKING BLACK
	INK MARKING BLUE
	INK MARKING WHITE
MEYER CO	COATING E28-4
MEYER CO	TAPE MYLAR ALUMINIZED
	TAPE MYLAR PS ADHESIVE
MEYERCORD CO	TAPE MYLAR/POLYESTER PS
MFE CORP	RECORDER STRIP CHART/THERMAL/2 CHANNEL
MICA CORP	COATING RESIN LIQUID TYPE MC6
	INSULATION MICA MUSCOVITE
	LAMIN MICAPLY EG818T
	LAMIN POLYIMIDE/GLASS
	LAMIN POLYIMIDE/GLASS MICAPAK PG402T
MICRO MEASUREMENTS	ADHESIVE AE10 EPOXY
	ADHESIVE M-BOND
	ADHESIVE M-BOND 200
	ADHESIVE M-BOND 43B
	ADHESIVE M-BOND 600
	ADHESIVE M-BOND 610
	ADHESIVE M-BOND A12
	ADHESIVE M-BOND AE15
	ADHESIVE M-BOND GA100
	ADHESIVE M-BOND GA2
	ADHESIVE M-BOND GA61
	LAMIN EPOXY/GLASS/PHENOLIC ME449-0141
MICRO SWITCH	MICROSWITCH WITH KEYS
MICRO-CIRCUITS	COATING EPOXY 18 SERIES CONDUCTIV
MICROSEAL CO	SEALANT MICROSEAL
MIDDLETOWN	CABLE TIES NOMEX/POLYETHYLENE FC4101
MIDLAND COLOR	INK 57377 YELLOW/K10 PAPER
	INK 61121 BROWN
MIDWEST PAINT	COATING MC7755-03 K1041 POLYURETHANE
	COATING MC7755-03 TOPCOAT DC3140
	LAMIN EPOXY/GLASS K1041 POLYURETHANE COATED
MILIBRIDE DIV	WIRE ELEC 2-WIRE CABLE
MILLER	RUBBER VITON V747-75
	RUBBER VITON V884-75
MILLER DIAL	DECAL FOTOFOIL P
MILLER MORTON CO	LIPBALM CHAPSTICK
MILLER SALES CO	TUBING PTFE SHRINKABLE
MILLER STEPHENSON	COATING URETHANE MS470
	CU CLAD FR4/PCB WITH MS-470 COATING
	LUBE FLUOROCARB MS136 TELOMER
	LUBE TFE FLUOROCARBON TELOMER
	MOLD RELEASE AGENT TFE MS-122
	RELEASE AGENT MS143
MINCO PRODUCTS	ADHESIVE MINCO 21365/7-1
	HEATER STRIP HK607005A 24AWG
	HEATER STRIP HK607005B
	HEATER STRIP/KAPTON 24 AWG
MINIGRIP	BAG MINIGRIP POLYETHYLENE
	BAG RECLOSABLE POLYURETHENE
MINOR RUBBER CO	RUBBER NEOPRENE ZX2002
	RUBBER SILICONE 2850R
	RUBBER SYNTHETIC MS35489
MIRACLE ADHESIVES CORP	ADHESIVE MIRACLE 40 PLUS
	ADHESIVE MIRACLE ALL PURPOSE CONSTRUCTION ADHESIVE

MSFC-HDBK-527 REV F 9999942 0006931 9

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
MIRACLE ADHESIVES CORP	ADHESIVE MIRACLE BLACK MAGIC TYPE "M"
	ADHESIVE MIRACLE CA25
	ADHESIVE MIRACLE CEILING TILE ADHESIVE
	ADHESIVE MIRACLE CLEAR SEALANT
	ADHESIVE MIRACLE CONTACT CEMENT
	ADHESIVE MIRACLE D518
	ADHESIVE MIRACLE D617
	ADHESIVE MIRACLE D618
	ADHESIVE MIRACLE DSA20
	ADHESIVE MIRACLE DSA40
	ADHESIVE MIRACLE GAUGED SLATE ADHESIVE
	ADHESIVE MIRACLE HT4620
	ADHESIVE MIRACLE L2000N FACING ADHESIVE
	ADHESIVE MIRACLE L3000 FACING ADHESIVE
	ADHESIVE MIRACLE LA69
	ADHESIVE MIRACLE LA76
	ADHESIVE MIRACLE LATEX CAULK 'N GLUE
	ADHESIVE MIRACLE MA200
	ADHESIVE MIRACLE MA222
	ADHESIVE MIRACLE MA76
	ADHESIVE MIRACLE MS120
	ADHESIVE MIRACLE MS130 "SAFE 'N SOUND"
	ADHESIVE MIRACLE NON-FLAMMABLE CONTACT CEMENT
	ADHESIVE MIRACLE PANEL FOAM AND CONSTRUCTION ADHESIVE
	ADHESIVE MIRACLE PF101
	ADHESIVE MIRACLE PF102
	ADHESIVE MIRACLE PF88
	ADHESIVE MIRACLE PF92
	ADHESIVE MIRACLE PF95
	ADHESIVE MIRACLE PF97
	ADHESIVE MIRACLE RESIN NP428
	ADHESIVE MIRACLE SCS100
	ADHESIVE MIRACLE SFA66
	ADHESIVE MIRACLE WALLBOARD ADHESIVE
	ADHESIVE MIRAPOXY MA800
MIRREX CORP	FILM MYLAR MIRROR REFLECT
MITHRA	ADHESIVE CERAMIC MITHRA 200
MITSUBISHI	BELT (TIMING) POLYURETHANE
	PLASTIC IUPILON POLYCARBONATE
	PLASTIC NOBLEN BC1
	PLASTIC NOBLEN BC2
	PLASTIC NOBLEN BC2A
	PLASTIC NOBLEN BC3
	PLASTIC NOBLEN BC3B
	PLASTIC NOBLEN BC4
	PLASTIC NOBLEN BC4C
	PLASTIC NOBLEN BC5C
	PLASTIC NOBLEN BC6
	PLASTIC NOBLEN BC8
	PLASTIC NOBLEN BC8B
	PLASTIC NOBLEN BC8C
	PLASTIC NOBLEN EC8
	PLASTIC NOBLEN EC9
MITSUBISHI	PLASTIC NOBLEN EC9B
	PLASTIC NOBLEN EX6
	PLASTIC NOBLEN GX20J
	PLASTIC NOBLEN JF40M
	PLASTIC NOBLEN JL20
	PLASTIC NOBLEN MA2
	PLASTIC NOBLEN MA3
	PLASTIC NOBLEN MA3N
	PLASTIC NOBLEN MA4
	PLASTIC NOBLEN MA7
	PLASTIC NOBLEN MA8
	PLASTIC NOBLEN MG3B
	PLASTIC NOBLEN MH4
	PLASTIC NOBLEN MH6
	PLASTIC NOBLEN MH8
	PLASTIC NOBLEN MK3G
	PLASTIC NOBLEN MK3H
	PLASTIC NOBLEN MX3A
	PLASTIC NOBLEN X1A
	PLASTIC NOBLEN X1B
	PLASTIC NOVATEC-L F101A
	PLASTIC NOVATEC-L F121
	PLASTIC NOVATEC-L F131
	PLASTIC NOVATEC-L F141
	PLASTIC NOVATEC-L F155
	PLASTIC NOVATEC-L F161
	PLASTIC NOVATEC-L F250
	PLASTIC NOVATEC-L F261
	PLASTIC NOVATEC-L FL00
	PLASTIC NOVATEC-L L300
	PLASTIC NOVATEC-L L320
	PLASTIC NOVATEC-L L330
	PLASTIC NOVATEC-L M400
	PLASTIC NOVATEC-L M420
	PLASTIC NOVATEC-L M430
	PLASTIC NOVATEC-L M450
	PLASTIC NOVATEC-L M460
	PLASTIC YUKALON AH-40
	PLASTIC YUKALON EC-51B
	PLASTIC YUKALON EC-70
	PLASTIC YUKALON EH-30
	PLASTIC YUKALON HE-30
	PLASTIC YUKALON HE-40
	PLASTIC YUKALON HE-60
	PLASTIC YUKALON LK-30
	PLASTIC YUKALON LK-50
	PLASTIC YUKALON LM-30
	PLASTIC YUKALON LM-31
	PLASTIC YUKALON LM-40
	PLASTIC YUKALON LS-30
	PLASTIC YUKALON MS-30
	PLASTIC YUKALON MT-30
	PLASTIC YUKALON MV-30
	PLASTIC YUKALON NF40
	PLASTIC YUKALON NH-50

MSFC-HDBK-527 REV F 9999942 0006932 0

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
MITSUBISHI	PLASTIC YUKALON YF-30
	PLASTIC YUKALON YK-30
	PLASTIC YUKALON YK-50
	PLASTIC YUKALON YK-60
	PLASTIC YUKALON YM-61
	PLASTIC YUKALON ZC-30
	PLASTIC YUKALON ZC-52
	PLASTIC YUKALON ZE-41
	PLASTIC YUKALON ZE-61
	PLASTIC YUKALON ZF-30
	PLASTIC YUKALON ZF-50
	PLASTIC YUKALON ZF-51
	PLASTIC YUKALON ZF-52
	PLASTIC YUKALON ZF-53
MMC	INSULATION FOAM CPR488 NET SPRAY
	TEFLON PTFE RESIN (POWDERED RAW)
MMC-MAF	CABLE HARNESS ASSEMBLY QUIRK 22AWG
MMMA-MAF	INSULATION FOAM POUR EXP1
MOBAY CHEMICAL	INSULATION FOAM URETHANE CMHR
	PLASTIC BAYBLEND
	PLASTIC BAYBLEND DP2-1439
	PLASTIC BAYBLEND DP2-1440
	PLASTIC BAYBLEND DP2-1441
	PLASTIC BAYBLEND DP2-1482
	PLASTIC BAYBLEND DP2-1483
	PLASTIC BAYBLEND DP2-1484
	PLASTIC BAYBLEND MC2500
	PLASTIC BAYBLEND MC3200
	PLASTIC BAYBLEND MH6570
	PLASTIC BAYBLEND MH6580
	PLASTIC BAYBLEND MH6595
	PLASTIC BAYBLEND MJ2500
	PLASTIC BAYBLEND UT1018
	PLASTIC MERLON 1143
	PLASTIC MERLON 2407
	PLASTIC MERLON 2458
	PLASTIC MERLON 5V-6485
	PLASTIC MERLON 6355
	PLASTIC MERLON 6455
	PLASTIC MERLON 6655
	PLASTIC MERLON 6680
	PLASTIC MERLON 9415
	PLASTIC MERLON AL400 1068 TINT
	PLASTIC MERLON FCR-2405
	PLASTIC MERLON FCR-6255
	PLASTIC MERLON HMS 3318
	PLASTIC MERLON M39 (L)
	PLASTIC MERLON M40 (H)
	PLASTIC MERLON M40 (L)
	PLASTIC MERLON M50 (H)
	PLASTIC MERLON M50 (L)
	PLASTIC MERLON RX3 1113 TINT
	PLASTIC MERLON SF-600 0.25 INCHES
	PLASTIC MERLON SF-800 0.25 INCHES
	PLASTIC MERLON SF-810 0.25 INCHES
MOBAY CHEMICAL	PLASTIC MERLON SF-820 0.24 INCHES
	PLASTIC MERLON T-85
	PLASTIC MERLON T-95
	PLASTIC NYDUR BC 303
	PLASTIC NYDUR BC 402
	PLASTIC NYDUR BKV 130
	PLASTIC NYDUR BKV 140
	PLASTIC PETLON 3530
	PLASTIC PETLON 4530
	PLASTIC PETLON 7530
	PLASTIC POCAN B1505
	PLASTIC POCAN B3225
	PLASTIC POCAN B3235
	PLASTIC POCAN B4225
	PLASTIC POCAN B4235
	PLASTIC POCAN S1506
MOBIL OIL CORP	COATING WATER-ACRYLIC ENAMEL BLUE
	GREASE MOBIL 28
	PLASTIC OS 2824
	PLASTIC PS MX7100A
	PLASTIC PS1400
	PLASTIC PS2124
	PLASTIC PS3654
	PLASTIC PS3824
	PLASTIC PS4154
	PLASTIC PS4324
	PLASTIC PS4600
	PLASTIC PS5400
	PLASTIC PS8120
	PLASTIC PS9524
MOBILE INDUSTRY SAFE	EARPLUGS 4560
MOHAWK MILLS	FABRIC HT-2002 ARAMID/KNIT MESH
MOLDEX	NYLON 6/6
	NYLON PLASTIC
MOLEX INC	CONNECTOR TAPE RECORDER
MONOMER-POLYMER AND DAJAC LABS	ADHESIVE EPIPHEN 825B
MONSANTO	COATING PHENOLIC SC 1008
	INSULATION FOAM SKYBOND POLYIMIDE
	MOLD COMPOUND POLYPRO
	NYLON 6/6
	PLASTIC CADON 112
	PLASTIC CADON 127
	PLASTIC CADON 135PG
	PLASTIC CADON 140
	PLASTIC CADON 160
	PLASTIC CADON 161
	PLASTIC CADON 2100
	PLASTIC CADON FRX
	PLASTIC CADON G1606
	PLASTIC CADON G2110
	PLASTIC CADON G2120
	PLASTIC KOSTIL AF1/PA
	PLASTIC KOSTIL AF3/PA
	PLASTIC KOSTIL AFL1/PA

MSFC-HDBK-527 REV F 9999942 0006933 2

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
MONSANTO	PLASTIC KOSTIL BF/PA
	PLASTIC LUSTRAN ABS1148
	PLASTIC LUSTRAN ABS248
	PLASTIC LUSTRAN ABS448
	PLASTIC LUSTRAN ABS648
	PLASTIC LUSTRAN ABS743
	PLASTIC LUSTRAN ABS911
	PLASTIC LUSTRAN ABS914HM
	PLASTIC LUSTRAN ABS921UV
	PLASTIC LUSTRAN ABSPG298 PLATED
	PLASTIC LUSTRAN ABSPG298 UNPLATED
	PLASTIC LUSTRAN ELITE LGM
	PLASTIC LUSTRAN ULTRA HX
	PLASTIC LUSTRAN ULTRA MX
	PLASTIC TRIAZ 1120
	PLASTIC TRIAZ 1125
	PLASTIC VYDYNE 21
	PLASTIC VYDYNE 21SP
	PLASTIC VYDYNE 21X
	PLASTIC VYDYNE 22H
	PLASTIC VYDYNE 22HSP
	PLASTIC VYDYNE 24NSP
	PLASTIC VYDYNE 25W
	PLASTIC VYDYNE 60H
	PLASTIC VYDYNE 65B
	PLASTIC VYDYNE 66B
	PLASTIC VYDYNE 909
	PLASTIC VYDYNE M340
	PLASTIC VYDYNE M344
	PLASTIC VYDYNE M345
	PLASTIC VYDYNE R-100
	PLASTIC VYDYNE R-200
	PLASTIC VYDYNE R-220
	PLASTIC VYDYNE R-250
	PLASTIC VYDYNE R-400
	PLASTIC VYDYNE R-513
	PLASTIC VYDYNE R-513H
	PLASTIC VYDYNE R-533
	PLASTIC VYDYNE R-533H
	PLASTIC VYDYNE R-538H-02
	PLASTIC VYDYNE R-543
	PLASTIC VYDYNE R-543H
	RUBBER SANTOPRENE
MONTEDISON	LUBE GREASE FOMBLIN Z-LHT
	LUBE OIL FOMBLIN Y06
	LUBE OIL FOMBLIN Y16
MONTEFLUOUS	LUBE GREASE Y VAC 3
MONTROSE PRODUCTS	CABLE COAXIAL RG-58C/U
MOOG INDUSTRY	FABRIC NYLON BUNA-N REINFORCED
	RUBBER VITON FLUID RESISTANT
MORTON CHEMICAL DIVISION, MTI	ADHESIVE PRESSURE SENSITIVE
MORTON CHEMICALS	MOLD COMPOUND EPOXY EMC 480
MORTON THIOKOL	CORE ASSEMBLY 7U82634
	INSULATION FOAM CPR1061 WITH ALBICOTE FRL
MOSITES RUBBER	FABRIC KEVLAR/FLUOREL
	RUBBER FLUOREL 1062
	RUBBER FLUOREL 1079K
	RUBBER FLUOROELASTOMER 2401B
	RUBBER MOSITES 10238
	RUBBER NEOPRENE 60382
	RUBBER SILICONE 14140D
	SPONGE RUBBER SILICONE 14143
	SPONGE RUBBER VITON 1028
MOSS SEAL CO	RUBBER VITON O-RING 2-904
MOTOROLA	INSULATION FOAM ABLESTICK/ECCOSPHERES S1
	WIRE ELEC P/N ON365474-1
MOXNESS	HOSE SILICONE MS70G31
	HOSE SILICONE/PBI POS BREATHER
	MULTI-LAYERED TFE TAPE/CLAMP
	SINGLE LAYER TAPE/BENDIX CLAMP
	TAPE ADHESIVE SILICONE GLASS/REINFORCED
	TAPE SILICONE MOX/FIBERGLASS
	TAPE SILICONE SB1050Y/SB1050
	TAPE STRETCH SILICONE RUBBER
	TAPE VITON-FLUOREL/CLAMP
	TUBING SILICONE MS50G38
MULTIWIRE	LAMIN EPOXY/GLASS FIBER
MULTIWIRE/COLUMBIA	CONNECTOR CIRCUIT BOARD FR4 DOUBLE WIDTH
TECH CORP	FLIGHT WITH HUMISEL 1B31 ACRYLIC TYPE AR
	CONFORMAL COATING
N L INDUSTRIES	CERAMIC AB312 FABRIC/POLYETHYLENE
	COATING SILCARB/POLYETHYLENE
NA-TEX CORP	FABRIC COTTON CHEESE CLOTH
NALGE DIV, SYBRON CORP	CONNECTOR POLYPROPYLENE #6151
NALGENE	NALGENE MA 255 TYPE 4
NARMCO	ADHESIVE METLBOND 1133 FOAM
	ADHESIVE METLBOND 306/112 FOAM
	ADHESIVE METLBOND 328
	ADHESIVE METLBOND 329 EPOXY FILM
	ADHESIVE METLBOND 6607 FOAM EPOXY
	COATING 6725-1 PRIMER
	COMPOSITE 5245C RESIN/IMG FIBR
	FABRIC NARMCO 3200/120
	FABRIC NARMCO 506 GLASS PHENOL
	FILM METLBOND 1113-2 ADHESIVE
	LAMIN EPOXY/GLASS
	LAMIN EPOXY/GRAPHITE 3501/AS
	LAMIN EPOXY/GRAPHITE 5208/T300
	LAMIN EPOXY/KEVLAR 570PR0/49-181 KEVLAR
	LAMIN NARMCO 3203-1581 EPOXY
NARROW FABRIC INDUSTRIES	FABRIC ELASTIC 0.75 WIDE
NASA	FABRIC NOMEX TWILL 6.5 OZ
	FILM CRONOPAQUE PETP/VINYL
	RUBBER NEOPRENE SN100
	SOAP NON-FOAMING
NASA/GSFC	COATING INORGANIC WHITE
	CONNECTOR ELECTRICAL
NASA/JPL	LAMIN EPOXY/GLASS/RL4389 COATED

MSFC-HDBK-527 REV F 9999942 0006934 4

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
NASA/JPL	TUBING POLYOLEFIN HST CLEAR
NASA/JSC	CABLE EIM
	CABLE OSCILLOSCOPE
	HEADBAND HEADSET MX2506/AIC
	INSULATION FOAM POLYURETHANE VALSALVA
	RUBBER NEOPRENE
	RUBBER NEOPRENE NS101
	RUBBER NEOPRENE NS105B
	RUBBER NEOPRENE NS107
	RUBBER NEOPRENE NS111
NASA/KSC	CONNECTOR ELECTRICAL
	HOSE TEFLON LINER (PROTION FROM HYDROCARBON SAMPLE LINE)
	INSULATION WIRE GREEN (PORTION FROM HYDROCARBON SAMPLE LINE)
	INSULATION WIRE WHITE (PORTION FROM HYDROCARBON SAMPLE LINE)
	RED SHIELDING/SHEATH MATERIAL (PORTION FROM HYDROCARBON SAMPLE LINE)
	RETENTION OF HCI ON LAUNCH PLUME SAMPLER CHEMICAL FILTERS
	RUBBER OUTERWIRE CASING BLACK (PORTION FROM HYDROCARBON SAMPLE LINE)
	TAPE LACING (PORTION FROM HYDROCARBON SAMPLE LINE)
	TAPE WHITE WRAPPING (PORTION FROM HYDROCARBON SAMPLE LINE)
NASA/MSFC	CABLE ELEC NILCO/TFE/NYLON/NOMEX/AL
	COVER DUST FES BETA/VELCRO
	FLIGHT DATA FILE WITH BOOKS
	O-RINGS SPARE FOR FES FURNACE
NASHUA CORP	TAPE 322 AL FOIL/ADHESIVE
	TAPE FR357 ADHESIVE WITH BACKING
NATIONAL BERYLLIA	POTTING COMPOUND BERLON E0383
	POTTING COMPOUND BERLON E33
NATIONAL DISTILLERS & CHEMICAL	PLASTIC PETROTHENE LB 603
	PLASTIC PETROTHENE LB 851
	PLASTIC PETROTHENE LB 861
	PLASTIC PETROTHENE LS 404
	PLASTIC PETROTHENE LS 506
	PLASTIC PETROTHENE LS 509
	PLASTIC PETROTHENE LS 511
	PLASTIC PETROTHENE LS 514
	PLASTIC PETROTHENE LS 523
	PLASTIC PETROTHENE LS 525
	PLASTIC PETROTHENE LS 528
	PLASTIC PETROTHENE LS 530
	PLASTIC PETROTHENE LS 545
	PLASTIC PETROTHENE LS 556
	PLASTIC PETROTHENE LS 606
	PLASTIC PETROTHENE LS 609
	PLASTIC PETROTHENE LS 618
	PLASTIC PETROTHENE LS 630
	PLASTIC PETROTHENE LS 901
	PLASTIC PETROTHENE LY 656
NATIONAL DISTILLERS & CHEMICAL	PLASTIC PETROTHENE NA 117
	PLASTIC PETROTHENE NA 202
	PLASTIC PETROTHENE NA 208
	PLASTIC PETROTHENE NA 213
	PLASTIC PETROTHENE NA 225
	PLASTIC PETROTHENE NA 226
	PLASTIC PETROTHENE NA 241
	PLASTIC PETROTHENE NA 246
	PLASTIC PETROTHENE NA 249
	PLASTIC PETROTHENE NA 254
	PLASTIC PETROTHENE NA 270
	PLASTIC PETROTHENE NA 295
	PLASTIC ULTRATHENE UE 631 19% VA
	PLASTIC ULTRATHENE UE 633 19% VA
	PLASTIC ULTRATHENE UE 635 9% VA
	PLASTIC ULTRATHENE UE 637 9% VA
	PLASTIC ULTRATHENE UE 655 9% VA
	PLASTIC ULTRATHENE UE 657 12% VA
NATIONAL FILTER CORP	FABRIC FELT NYLON 236-006-03
NATIONAL METALLIZING	FILM 43/82/2 KAPTON/NOMEX/AU
	FILM KAPTON AL/BETA 107/GLASS
	FILM KAPTON ALUMINIZED
	FILM KAPTON/BETA 107 POLYESTER FR
	FILM KAPTON/GLASS/BETA 107 BLK
	FILM MYLAR ALUMINIZED
	FILM NM50-13 KAPTON/NOMEX
	FILM NM50-48 KAPTON/AL/ORGANIC COATED
	FILM NM50-49 KAPTON GOLDIZED
	FILM NM50-67 KAPTON AL/ORGANIC COATED
	FILM NM54-15 KAPTON AL/ORGANIC COATED
	FILM POLYIMIDE ALUMINIZED
	INSULATION MYLAR ALUMINIZED TYPE 2
	STRAP ELEC AL KAPTON/PBI
	TAPE ALUMINIZED KAPTON 14162-51
	TAPE NM53-57 KAPTON/AL ORGANIC COATED
	TAPE POLYIMIDE AU/AL PS ADHESIVE
	TAPE POLYIMIDE T966
NATIONAL PAINT AND VARNISH	COATING ENAMEL 3C-31 POLYURETHANE WHITE
NATIONAL PROCESS IND	LUBE DRY NPI14
	LUBE DRY NPI425 POLYIMIDE
	LUBE DRY VITROLUBE 1220
	LUBE DRY VITROLUBE 2500 INORGANIC
NATIONAL SEAL	RUBBER FLUOREL V23
NATIONAL STARCH AND CHEMICAL	ADHESIVE BONDMASTER 4500+
	ADHESIVE BONDMASTER 81-0590
	ADHESIVE BONDMASTER E645
	ADHESIVE BONDMASTER G781
	ADHESIVE BONDMASTER M606
	ADHESIVE BONDMASTER M620
	ADHESIVE BONDMASTER M666
	ADHESIVE BONDMASTER M688 CH16
	ADHESIVE BONDMASTER M688 CH8
	ADHESIVE BONDMASTER M777 A/B EPOXY
	LAMIN EPOXY/PHENOLIC M602

MSFC-HDBK-527 REV F 9999942 0006935 6

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
NAVAL RESEARCH LAB	MULTI-LAYERED INSULATION BLANKET
NAZ DAR	COATING NAZDAR ER111
	INK NAZDAR ER112 EPOXY
NEC	RESIN SDP 1 SHEET DAMPING MATERIAL
	RESIN SDP 1A POLYETNER EPOXY WITH PHTHALIC
	ACID ANHYDRIDE HARDENER
	RESIN SDP 2 BIS PHENOL A DAMPING MATERIAL
	RESIN SDP 3 BROMINATED EPOXY WITH
	POLYAMIDEAMINE HARDENER
	RESIN SDP 3A BROMINATED EPOXY WITH
	POLYAMIDEAMINE HARDENER
	RESIN SDP 4 BROMINATED EPOXY WITH
	POLYOXYARKYLENE POLYAMINE HARDENER
NELCO PRODUCTS	LAMIN EPOXY/GLASS
	LAMIN EPOXY/GLASS COATED WITH CE1155
	LAMIN EPOXY/GLASS N4105
NELSON NAMEPLATE CO	NAMEPLATES SSME
NEW ENGLAND TAPE CO	TAPE 925 ALUMINUM WITH POLYESTER ADHESIVE
NICHOLS ENGINEERING	RUBBER FLUOROSILICONE NE6060
	RUBBER FLUOROSILICONE NE7070G
	RUBBER PNF P39
	RUBBER SILICONE NE6071/6071
	TUBING VITON V138A
NICOLET PAPER CO	PAPER ESP-14
NIHON VALCA	TUBING PTFE NON-HEAT SHRINK
NIHON YUSHI	COATING EPICO 2000 (SG054, SG116) EPOXY
	PAINT
NIKON	CABLE ELEC CAMERA/PVC INSULATION
	RUBBER NEOPRENE
	WIRE ELEC VARGLAS SLEEVE
NIMET IND	COATING NYTUFF TEFLON ANODIZED
	COATING TEFLON INFUSED
NIPPON AVIOTRONICS	LAMIN EPOXY/GLASS CIRCUIT BOARD
	LAMIN EPOXY/GLASS PC BOARD
NIPPON CARBON CO	FABRIC NICALON SILCN CARB INOR
NIPPON ROCKTIGHT CO	ADHESIVE LOCTITE AV
NIPPON VALGUA IND	RUBBER VITON
NISSEI ELECTRIC CO	CABLE ELEC EF-2PWMS HIFLON
	CABLE F-12PWMS HIFLON
NOAH LAMPORT	FABRIC NOMEX 7878 G650
	FABRIC NOMEX 7878 G650/FC5
NORCHEM	PLASTIC 1013(1)
	PLASTIC 1014(1,2)
	PLASTIC 1015
	PLASTIC 1016(1,3)
	PLASTIC 1017
	PLASTIC 1103(1)
	PLASTIC 1105(1)
	PLASTIC 1510HC
	PLASTIC 1510LC
	PLASTIC 2000GJ
	PLASTIC 2004MR
	PLASTIC 2085CW
	PLASTIC 3002GJ
	PLASTIC 3010
NORCHEM	PLASTIC 3011SO
	PLASTIC 3012
	PLASTIC 3050
	PLASTIC 3060
	PLASTIC 3070
	PLASTIC 3080
	PLASTIC 3303SK
	PLASTIC 3304(4)
	PLASTIC 331050
	PLASTIC 3312
	PLASTIC 3420CK
	PLASTIC 3510HC
	PLASTIC 5003
	PLASTIC 5204
	PLASTIC 5205
	PLASTIC 5207
	PLASTIC 5210
	PLASTIC 5218
	PLASTIC 5225
	PLASTIC 5240
	PLASTIC 5260
	PLASTIC 5405
	PLASTIC 5406G
	PLASTIC 5408G
	PLASTIC 5411G
	PLASTIC 5602
	PLASTIC 5603
	PLASTIC 5604
	PLASTIC 5701
	PLASTIC 5703
	PLASTIC 5704 (2)
	PLASTIC 5705 (2)
	PLASTIC 5707
	PLASTIC 5713
	PLASTIC 6001C2
	PLASTIC 6003
	PLASTIC 6004
	PLASTIC 6007
	PLASTIC 6009
	PLASTIC 6206
	PLASTIC 6230
	PLASTIC 7001DJ
	PLASTIC 7200AF
	PLASTIC 7300GF
	PLASTIC 7300KF
	PLASTIC 8000GK
	PLASTIC 8001KL
	PLASTIC 8004MR
	PLASTIC 8004ZR
	PLASTIC 8020GU
	PLASTIC 8080GW
	PLASTIC 8310GO
	PLASTIC 8310KO
	PLASTIC 8402TO
	PLASTIC 8420HK

MSFC-HDBK-527 REV F 9999942 0006936 8

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
NORCHEM	PLASTIC 8462HR
	PLASTIC 8470HU
	PLASTIC 8502HK
	PLASTIC 8602HJ
	PLASTIC 8752HF
	PLASTIC 8755HK
	PLASTIC 8762HR
	PLASTIC 8770HU
NORDIC	KEL-F 81
NORPLEX OAK INDUSTRIES	LAMIN EPOXY/GLASS G10FR/SR240
	LAMIN EPOXY/GLASS/DC3140 COATED
	LAMIN STYRENE/GLASS REXOLITE 2200
NORTH AMERICAN PHILIPS CO	RAZOR NORELCO ROTARY WITH CHARGER
NORTH CAROLINA FOAM	INSULATION FOAM NCFI 22 65
	INSULATION FOAM NCFI 23 38 MMC
	INSULATION FOAM NCFI 23 58 POLYISOCYANURATE
	INSULATION FOAM POLYISOCYANURATE NCFI 23 66
NORTHERN PETROCHEMICAL CO	ADHESIVE MELTHENE M1310
	ADHESIVE MELTHENE M5001
	ADHESIVE MELTHENE M5002
	ADHESIVE MELTHENE M5004
	ADHESIVE MELTHENE M5030
	ADHESIVE MELTHENE M5311
	ADHESIVE MELTHENE M5331
	ADHESIVE MELTHENE M5400
NORTON	ADHESIVE CHEMGRIP 34
	ADHESIVE TYGOBOND 50
	GLOVE RUBBER E-091 VITON
	TUBING PTFE HST
	TUBING TYGON B44-3
	TUBING TYGON S54HL
NOXELL CORP	MASCARA LONG-NLUSH BLACK/BROWN
NUODEX INC	PLASTIC VESTODUR 1000
	PLASTIC VESTODUR 2000
	PLASTIC VESTODUR 2000 SO
	PLASTIC VESTODUR 3000
	PLASTIC VESTODUR GK 30
	PLASTIC VESTODUR MGF 30
	PLASTIC VESTODUR MIN 125
	PLASTIC VESTODUR SGF 15
	PLASTIC VESTODUR SGF 20
	PLASTIC VESTODUR SGF 20 SO
	PLASTIC VESTODUR SGF 30
	PLASTIC VESTODUR SGF 30 SO
	PLASTIC VESTODUR SGF 50
	RUBBER VESTAMID E40-S3
	RUBBER VESTAMID E47-S3
	RUBBER VESTAMID E50-C5-S2
	RUBBER VESTAMID E55-S3
	RUBBER VESTAMID E57-C5-S2
	RUBBER VESTAMID E62-S3
	RUBBER VESTAMID E67-C5-S2

MANUFACTURER	DESIGNATION
NUPLA CORP	COMPOSITE EPOXY FIBERGLS A8514
NUPRO COMPANY	RUBBER VITON FLUID RESISTANT
	RUBBER VITON O-RING
NVF CO	LAMIN G7-832
	LAMIN MELAMINE/GLASS G5-813
	LAMIN MELAMINE/GLASS G9-818
NYCOTE LABORATORIES	VARNISH NYLON 7-11
NYLOK-DETROIT CORP	SEALANT THREAD VC3
NYTEF PLASTICS, LTD.	PLASTIC ACETAL COPOLYMER
	PLASTIC ACETAL GLASS FILLED
	PLASTIC ACETAL HOMOPOLYMER
	PLASTIC NORYL
	PLASTIC NYLON 6/12
	PLASTIC NYLON MP/FILLED
	PLASTIC NYLON NAST TYPE 6
OAK INDUSTRIES	ADHESIVE CMC19-2
	ADHESIVE CMC634-2
	ADHESIVE FILM CMC122
	FABRIC FLUORGLAS 2812
	FABRIC FLUORGLAS 2815 TFE/SILICONE
	FABRIC M380-3 FIBERGLASS/TFE
	FABRIC TEFLON/COATED BETA CLOTH
	FILM KODAR 6763
	LACING TAPE PTFE/GLASS
	LAMIN CMC608-2 POLYIMIDE WITH COPPER
	OAK BOARD COATED WITH KPR
	TAPE ALUMINUM FOIL/GLASS CLOTH 2922-7
	TAPE FLUORGLAS 2346-1 ADHESIVE
	TAPE PLASTIC
OAK-ATLANTIC	MOLD COMPOUND REXOLITE 1422 STYRENE
OAKLAND CORPORATION	SEALANT VIBRA-TITE ADHESIVE
ODETICS INC	COATING EPOXY A117-B
	COATING HUMISEAL 1B31 ACRYLIC
	COATING TRAIL CHEM PRIMER 20464-66
OHASHI CHEMICAL	COATING HAMMER NET 300 PAINT CAR WHITE
OIL CENTER RESEARCH	COATING WONDER/PRIMER 442-3B
OKONITE CO	TAPE OKONITE 35 JACKETING
OLYMPUS	TAPE CASSETTE MC60
OMNI SPECTRA	CONNECTOR 2001-5119-00
OPTICAL COATING LAB	COATING HEA LENS INORGANIC
	COATING HFA ANTIGLAR OPTICAL
ORCON CORP	FILM AL/TEDLAR/NYLON AN16
	TAPE KAPTON/AL METALIZED KN80
	TAPE KAPTON/NYLON ACRYLIC KN80
	TAPE KAPTON/NYLON ACRYLIC LOT 20
	TAPE KAPTON/NYLON OT21
ORGANIC PRODUCTS	INK F100 BLACK
	INK F600 MYLAR BLACK
	SEALANT TORQUE F900
OSAKA SODA CO	VARNISH DAISO DAP TYPE A
OWENS CORNING	COATING XECOTE/OCF4190B WITH F017A
	CORD FIBERGLASS RESIN TREATED
	FABRIC FG104 BETA F017A FINIS
	FELT BETA GLASS C3-21-109
	INSULATION FIBERGLASS BUILDING PINK

MSFC-HDBK-527 REV F 9999942 0006937 T

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
OWENS CORNING	INSULATION GLASS/PHENOLIC PEL05
	THREAD GLASS FIBER INORGANIC
OWENS ILLINOIS	COATING G650 FR WHITE
OXY METAL INDUSTRIES	DEVELOPER D-1
	DEVELOPER NQ-1
	PENETRANT FLUORESCENT P6F-4
	PENETRANT FLUORESCENT P6F-4L
	PENETRANT FLUORESCENT P6F-4LNC
P D GEORGE CO	COATING PEDIGREE 923 EPOXY VARNISH
	COATING TRITHERM 981 WIRE ENAMEL
	COATING VARNISH 961
P0109/P0209/P0203	ADHESIVE C9-4210 AND 4215/H3469 EPOXY
P0524/P1208	POTTING COMPOUND EE0004/HD3561
P1111/CAT33-P0724	INK L-O-N SERIES MARKING
PALL ULTRAFINE CORP	FILTER CARTRIDGE PTFE
PALMER IND	ADHESIVE BONDING 6035
PANDUIT	CABLE TIES PAN-TY HALAR
	CABLE TIES PAN-TY TEFZEL
PANELGRAPHIC CORP	PLASTIC LEXAN CHROMAFILTER LENS
	POLYCARBONATE
PARCO	RUBBER VITON 9009-75
	RUBBER VITON FLUID RESISTANT
PARKER HANNIFIN	HOSE PARFLEX 540N/POLYURETHANE
	HOSE PARFLEX 558H/POLYESTER
	RUBBER VITON 3-912V
	RUBBER VITON 3-916V
	RUBBER VITON 75
	RUBBER VITON FLUID RESISTANT
	RUBBER VITON O-RING S/A 2-212
	RUBBER VITON O-RING S/A2-214
	RUBBER VITON V747-75
	RUBBER VITON V884-75
	TEFLON TFE VIRGIN
PARKER LABORATORIES	COMPOUND ACROSONIC 100 GEL
PARKER PEN	INK PARKER/JCP E20
	PEN PARKER 6-234-8 BLACK
PARKER SEAL	LUBE PARKER O-LUBE SILICONE
	LUBE SUPER-O-LUBE
	RUBBER BUNA N 5-565
	RUBBER BUTYL B59L-80
	RUBBER BUTYL B612-70
	RUBBER CHLOROPRENE C873-70
	RUBBER EPR E515-80
	RUBBER EPR E529-6
	RUBBER EPR E617-9 ELASTOMER
	RUBBER EPR E688-70
	RUBBER EPR E692-75
	RUBBER EPR E740-75
	RUBBER EPR E798-70
	RUBBER EPR E810-80
	RUBBER FLUOROCARBON
	RUBBER FLUOROSILICONE L449-65
	RUBBER FLUOROSILICONE L677-70
	RUBBER FLUOROSILICONE L737-65
	RUBBER NEOPRENE C147-70
PARKER SEAL	RUBBER NEOPRENE C557-70
	RUBBER NITRILE
	RUBBER NITRILE N304-75
	RUBBER NITRILE N506-65
	RUBBER NITRILE N602-7
	RUBBER NITRILE N674-70
	RUBBER NITRILE N741-75
	RUBBER NITRILE N756-75
	RUBBER NITRILE N766-75
	RUBBER SILICONE NOC ZZ-R-765
	RUBBER SILICONE O-RINGS
	RUBBER SILICONE S317
	RUBBER SILICONE S383-70
	RUBBER SILICONE S455-70
	RUBBER SILICONE S469-40
	RUBBER SILICONE S604-70
	RUBBER SILICONE S614-80
	RUBBER SILICONE SE4404U WITH SIO2 FILLER
	RUBBER SR2702-75
	RUBBER VITON 744-75
	RUBBER VITON A V709-90
	RUBBER VITON A V745-75
	RUBBER VITON FLUID RESISTANT
	RUBBER VITON O-RING
	RUBBER VITON O-RING S/A 2-012
	RUBBER VITON O-RING S/A 2-014
	RUBBER VITON O-RING S/A 2-016
	RUBBER VITON O-RING S/A 2-020
	RUBBER VITON O-RING S/A 2-024
	RUBBER VITON O-RING S/A 2-035
	RUBBER VITON O-RING S/A 2-343
	RUBBER VITON O-RING V730-75
	RUBBER VITON V672-7
	RUBBER VITON V709-90
	RUBBER VITON V747-75
	RUBBER VITON V763-60
	RUBBER VITON V769-60
	RUBBER VITON V779-75
	RUBBER VITON V884-75
	RUBBER VITON V894-90
	SEALANT GASK-O-SEAL
PASSAIC RUBBER	TAPE RUBBER FLUOREL L2231
PATAGONIA	FABRIC BUNTING PANTS 31801
	FABRIC SHIRT
	SOCKS PATAGONIA
PAYTEL SYSTEMS	TAPE CASSETTE
PEABODY DORE	FLUOROGREEN E-600 TFE/GLASS
PEABODY NOISE CONTROL	SOUND INSUL KNM-50B
PELIKAN	INK PELIKAN 24 DIACETONE ALCOHOL
PELLON CORP	FABRIC PELLON #7015
	FABRIC PELLON FR 954
	FABRIC POLYESTER KK14 FR
PELMOR LABORATORIES	ADHESIVE VITON PLV2002
	FABRIC KEVLAR 1813-2 WITH VITON
	RUBBER VITON PLV2000

MSFC-HDBK-527 REV F 9999942 0006938 1

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
PENNTUBE PLASTICS	TUBING FEP 100 HST
	TUBING PTFE HST
	TUBING PTFE NON-HEAT SHRINK
	TUBING PTFE SHRINKABLE
	TUBING TEFLON FEP HST
	TUBING TEFLON FEP SMT HS
	TUBING TEFLON TFE HST
PENNWALT CORP	COATING 4367-3 ON LAMIN 515-700
	COATING 4699-121A/4334-109
	COATING ACRYLIC 3715-51-2B A-601
	COATING ACRYLIC 3715-52-1
	COATING EPOXY 3715-49-II A/B/C
	COATING GRAY TOPCOAT/KOROPON PRIMER
	COATING LATEX 3715-16-1 A/B EPOXY
	COATING LATEX 3715-24-1 A/B TC
	COATING LATEX 3715-25-2 A/B
	COATING LATEX 3715-26-1 A/B
	COATING LATEX 4367-3 UNPIGMENTED
	COATING LATEX 4699-121B
	COATING LATEX 4699-126
	COATING ONCOR M50 LATEX
	COATING ONCOR M50/ZNCHR 4334-109
	COATING PENNWALT 4699-121-A
	COATING PENNWALT 4699-122-A
	COATING RC9108 4334-112 WHITE
	COATING RC9108 EPOXY
	KYNAR 460
	KYNAR PLASTIC FLUORIDE
	PLASTIC KYNAR 461
	PLASTIC KYNAR 710
	PLASTIC KYNAR 720
	PLASTIC KYNAR 721
	PLASTIC KYNAR 723
	PLASTIC KYNAR 730
	PLASTIC KYNAR 736
	PLASTIC KYNAR 741
	SANITIZER AMMONIUM STERICIDE
	SOLUTION 12% STERICIDE
PENTAPCO INC	WEBBING POLYESTER 2276 ELASTIC
PENTEL CORP	INK PENTEL PEN S360 ALL TYPES
	PEN PENTEL S520 BLACK
	PEN PENTEL S520 BLUE
	PEN PENTEL S520 GREEN
	PEN PENTEL S520 RED
PENTUBE PLASTICS	TUBING TEFLON TFE HST
PERCY HARMS CORP	MOLD COMPOUND EPOXY-DRY EPOX/POLYES
PERMABOND	ADHESIVE 910
	ADHESIVE PERMABOND 101
	ADHESIVE PERMABOND 102
	ADHESIVE PERMABOND 105
	ADHESIVE PERMABOND 107
	ADHESIVE PERMABOND 108
	ADHESIVE PERMABOND 130
	ADHESIVE PERMABOND 200
	ADHESIVE PERMABOND 240

MANUFACTURER	DESIGNATION
PERMABOND	ADHESIVE PERMABOND 268
	ADHESIVE PERMABOND 747
	ADHESIVE PERMABOND 750
	ADHESIVE PERMABOND ESP108
	ADHESIVE PERMABOND ESP109
	ADHESIVE PERMABOND ESP110
	ADHESIVE PERMALOK 5M060
	ADHESIVE PERMALOK AL138
	ADHESIVE PERMALOK HH120
	ADHESIVE PERMALOK HH190
	ADHESIVE PERMALOK HH194
	ADHESIVE PERMALOK HH195
	ADHESIVE PERMALOK HL126
	ADHESIVE PERMALOK HM118
	ADHESIVE PERMALOK HM128
	ADHESIVE PERMALOK LM113
	ADHESIVE PERMALOK MM115
	ADHESIVE PERMALOK MM15
	ADHESIVE PERMALOK PAS10
	ADHESIVE POWERBOND 919
	ADHESIVE POWERBOND 920
	ADHESIVE POWERBOND 922
	ADHESIVE QUICKBOND 513
	ADHESIVE QUICKBOND 523
	ADHESIVE QUICKBOND 610
	ADHESIVE QUICKBOND 612
	ADHESIVE QUICKBOND 614/610
	ADHESIVE QUICKBOND 650
	ADHESIVE RI2
PERMACEL	ADHESIVE PERMACEL KAPTON
	FABRIC GLASS/SILICONE 562F
	FABRIC GLASS/SILICONE 564E
	TAPE DL279 SILICONE
	TAPE P051 ACRYLIC TRANSFER
	TAPE P100 ALUMINUM FOIL/GLASS CLOTH WITH SILICONE ADHESIVE
	TAPE P11 ALUMINUM FOIL
	TAPE P21 GLASS
	TAPE P211 GLASS/SILICONE ADHESIVE
	TAPE P212 GLASS/SILICONE ADHESIVE
	TAPE P213 GLASS ACRYLIC ADHESIVE
	TAPE P214 GLASS/ACRYLIC
	TAPE P221 KAPTON WITH SILICONE ADHESIVE
	TAPE P223 TEFLON/AG
	TAPE P224 KAPTON/ACRYLIC ADHESIVE
	TAPE P252 MYLAR PS
	TAPE P262 NOMEX ARAMID FLATBACK ELEC INSULATION/SILICONE ADHESIVE
	TAPE P263 NOMEX/ACRYLIC (CREPE)
	TAPE P2650 SILICONE RUBBER NON ADHESIVE
	TAPE P29 VINYL BLACK ELECTRIC
	TAPE P421 TEFLON SILICONE ADHESIVE
	TAPE P422 TEFLON/SILICONE
	TAPE P423 TFE/SILICONE
	TAPE P424 TEFLON

MSFC-HDBK-527 REV F 9999942 0006939 3

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
PERMACEL	TAPE P427 TEFLON
	TAPE P430 TEFLON WITH PS
	TAPE P440 TEFLON/GLASS
	TAPE P50 COTTON WITH RUBBER ADHESIVE
	TAPE P5001 SILICONE RUBBER/GLASS CLOTH/ SILICONE ASH
	TAPE P551B SILICONE
	TAPE P670 POLYETHYLENE
	TAPE P69 PS
	TAPE POLYPROPYLENE P910
	TAPE TEFLON
	WIRE ELEC WRAPPED IN P2650 SILICONE TAPE
PERSERVO PAINT	INSULATION FOAM CPR488/FRL3 AND PERSERVO COATED
PERVEL INDUSTRIES	FILM LH94-5 CLEAR
	FILM POLYURETHANE/CARBON LH86-13
	PAPER PERVEL LH8613
PETERSON CHEMICAL	VARNISH INSULON 100 EPOXY
PETRARCH SYSTEMS INC	PLASTIC RIMPLAST NYLON 12
	PLASTIC RIMPLAST NYLON 6/6
	PLASTIC RIMPLAST PTA 1201
	PLASTIC RIMPLAST PTA 1202
	PLASTIC RIMPLAST PTA 6601
	PLASTIC RIMPLAST PTA 6602
	PLASTIC RIMPLAST PTA 6631
	PLASTIC RIMPLAST PTEE 601
	PLASTIC RIMPLAST PTEE 602
	PLASTIC RIMPLAST PTSEBS 1204
	PLASTIC RIMPLAST PTSEBS 2204
	PLASTIC RIMPLAST PTUA 102
	PLASTIC RIMPLAST PTUA 103
	PLASTIC RIMPLAST PTUE 101
	PLASTIC RIMPLAST PTUE 102
	PLASTIC RIMPLAST PTUE 202
	PLASTIC RIMPLAST PTUE 203
	PLASTIC RIMPLAST PTUE 205
	PLASTIC RIMPLAST PTUE 302
	PLASTIC RIMPLAST PTUE 332
	PLASTIC RIMPLAST R1000
	PLASTIC RIMPLAST R5000
	PLASTIC RIMPLAST RF-1006
	PLASTIC RIMPLAST RF-5006
	PLASTIC RIMPLAST RL-4610
	PLASTIC RIMPLAST RL-4620
PETROLON INC	LUBE GREASE SLICK 50
PHILADELPHIA QUARTZ	SODIUM SILICATE(N) INORGANIC
PHILADELPHIA RESINS	COATING CHOCKFAST ORANGE PR610 TCF
PHILLIPS CHEMICAL	INK MARKING 44
	MILK OF MAGNESIA
	MOLD COMPOUND RYTON R-10
	MOLD COMPOUND RYTON R-4
	MOLD COMPOUND RYTON R-5
	MOLD COMPOUND RYTON R-6
	MOLD COMPOUND RYTON R-7
	PCB CONNECTOR/VALOX 420/RYTON

MANUFACTURER	DESIGNATION
PHILLIPS CHEMICAL	PLASTIC MARLEX 5502
	PLASTIC MARLEX 6003
	PLASTIC MARLEX 6007
	PLASTIC MARLEX BMN 55500
	PLASTIC MARLEX BMN TR880
	PLASTIC MARLEX CL100
	PLASTIC MARLEX CL50
	PLASTIC MARLEX EHM 6001
	PLASTIC MARLEX EHM 6006
	PLASTIC MARLEX EMN TR885
	PLASTIC MARLEX ER9-0002
	PLASTIC MARLEX ER9-0020
	PLASTIC MARLEX HHM 4515
	PLASTIC MARLEX HHM 4903
	PLASTIC MARLEX HHM 5202
	PLASTIC MARLEX HHM TR210
	PLASTIC MARLEX HHM TR226
	PLASTIC MARLEX HHM TR230
	PLASTIC MARLEX HHM TR232
	PLASTIC MARLEX HHM TR250
	PLASTIC MARLEX HHM TR416
	PLASTIC MARLEX HMN 4550
	PLASTIC MARLEX HMN 50100
	PLASTIC MARLEX HMN 5060
	PLASTIC MARLEX HMN 54140
	PLASTIC MARLEX HMN 5580
	PLASTIC MARLEX HMN 6060
	PLASTIC MARLEX HMN TR938
	PLASTIC MARLEX HMN TR942
	PLASTIC MARLEX HMN TR950
	PLASTIC MARLEX HMN TR954
	PLASTIC RYTON PPS
	PLASTIC RYTON R-10 5002C
	PLASTIC RYTON R-10 5004A
	PLASTIC RYTON R-10 7006A
	PLASTIC RYTON R-3
PHOENIX TRIMMING	WEBBING DACRON
	WEBBING TY WD901
PHOTO-SONICS INC	FILM MAGAZINE
	FILM MAGAZINE 16MM
PHOTOFABRICATION TECNOLOGY	FILM CUPRON PMPX-C .0002"
PHYSIO CONTROL	GEL ELECTRODE DERMA-JEL
PIERCE-ROBERTS	RUBBER FLUOREL FC2174
PIGMENT DISPERSIONS	PIGMENT GREEN GLOVE BLADDER
PILOT CORP	INK PILOT FINELINER SWPP BLACK
	INK PILOT FINELINER SWPP BLUE
	INK PILOT FINELINER SWPP GREEN
	INK PILOT FINELINER SWPP RED
	INK PILOT RAZOR POINT SW10PP
PINCHIN JOHNSON	LUBE DRY GRAPHITE/BINDEN PL94
PIONEER BALLOON CO	RUBBER LATEX DIAMOND CLEAR 11-INCH BALLOON
PIONEER INC	FABRIC DACRON FELT
PITTSBURG CORNING	INSULATION FOAMGLAS CELLULAR
PLASKON	MOLD COMPOUND DAP FS5 BLACK 8000

MSFC-HDBK-527 REV F 9999942 0006940 T

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
PLASKON	MOLD COMPOUND DAP FS80/GLASS FILLED
	MOLD COMPOUND S-8723 EPOXY
	PLASTIC PLASKON 1960
	PLASTIC PLASKON 1961
	PLASTIC PLASKON 1974
	PLASTIC PLASKON 1985
	PLASTIC PLASKON 2060
	PLASTIC PLASKON 2061
	PLASTIC PLASKON 3100
	PLASTIC PLASKON 3100-7150
	PLASTIC PLASKON 3100LS
	PLASTIC PLASKON 3130
	PLASTIC PLASKON 3200
	PLASTIC PLASKON 3200LS
	PLASTIC PLASKON 3200SF
	PLASTIC PLASKON 3300
	PLASTIC PLASKON 3300S
	PLASTIC PLASKON 3300SH
	PLASTIC PLASKON 4020
	PLASTIC PLASKON 5000
	PLASTIC PLASKON 5000-7097
PLASTIC & RUBBER CO	RUBBER BUTYL 823-70
	RUBBER SILICONE 1235-70
	RUBBER SILICONE 15130
	RUBBER SILICONE HARDNESS SHORE "A" 65-75
	RUBBER SILICONE PARCO 1235-70
	RUBBER SILICONE PRE100-40R
	RUBBER VITON 9009-75
	RUBBER VITON 9009-90
PLASTIC ENGINEERING	INSULATION PLENCO 1512 ALKYD/GLASS
	MOLD COMPOUND PLENCO 1528
	MOLD COMPOUND PLENCO 1532 POLYESTER
	PELLETHANE 2103 POLYETHER TUBE
	PLASTIC KRATON 2701
	PLASTIC PLENCO 00713
	PLASTIC PLENCO 00714
	PLASTIC PLENCO 00732
	PLASTIC PLENCO 00755
	PLASTIC PLENCO 00757
	PLASTIC PLENCO 01500
	PLASTIC PLENCO 01505
	PLASTIC PLENCO 01510
	PLASTIC PLENCO 01529
	PLASTIC PLENCO 01530
	PLASTIC PLENCO 01535
	PLASTIC PLENCO 01580
	PLASTIC PLENCO 01581
	PLASTIC PLENCO 02000
	PLASTIC PLENCO 02300
	PLASTIC PLENCO 023008
	PLASTIC PLENCO 02360
	PLASTIC PLENCO 02408
	PLASTIC PLENCO 02482
	PLASTIC PLENCO 02535
	PLASTIC PLENCO 02567

MANUFACTURER	DESIGNATION
PLASTIC ENGINEERING	PLASTIC PLENCO 02571
	PLASTIC PLENCO 02929
	PLASTIC PLENCO 02957
	PLASTIC PLENCO 03343
	PLASTIC PLENCO 03509
	PLASTIC PLENCO 03557
	PLASTIC PLENCO 03597
	PLASTIC PLENCO 04002
	PLASTIC PLENCO 04300
	PLASTIC PLENCO 04301
	PLASTIC PLENCO 04304
	PLASTIC PLENCO 04309
	PLASTIC PLENCO 04349
	PLASTIC PLENCO 04400
	PLASTIC PLENCO 04414
	PLASTIC PLENCO 04466
	PLASTIC PLENCO 04485
	PLASTIC PLENCO 04527
	PLASTIC PLENCO 04548
	PLASTIC PLENCO 04568
	PLASTIC PLENCO 05115
	PLASTIC PLENCO 05118
	PLASTIC PLENCO 06201
	PLASTIC PLENCO 06203
	PLASTIC PLENCO 06205
	PLASTIC PLENCO 06305
	PLASTIC PLENCO 06343
	PLASTIC PLENCO 06553
	PLASTIC PLENCO 06554
	PLASTIC PLENCO 06582/MX582
	PLASTIC PLENCO 07002
	PLASTIC PLENCO 07080
	PLASTIC PLENCO 07200
	PLASTIC PLENCO 07202
	PLASTIC PLENCO 07203
	PLASTIC PLENCO 07307
	PLASTIC PLENCO 07321
	PLASTIC PLENCO 07368
	PLASTIC PLENCO 07417
	PLASTIC PLENCO 07467
	PLASTIC PLENCO 07476
	PLASTIC PLENCO 07487
	PLASTIC PLENCO 07500
	PLASTIC PLENCO 07502
	PLASTIC PLENCO 07507
	PLASTIC PLENCO 07523
	PLASTIC PLENCO 07552
	PLASTIC PLENCO 07579
	PLASTIC PLENCO CELLULOSE-FILLED ALKYD
	PLASTIC PLENCO COPOLYMER ELECTRICAL
	PLASTIC PLENCO ELECTRICAL AND ELECTRONIC ALKYD
	PLASTIC PLENCO ELECTRICAL MOLDING COMPOUND
	PLASTIC PLENCO GENERAL PURPOSE ALKYD
	TUBING ESTANE

MSFC-HDBK-527 REV F 9999942 0006941 1

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
PLASTIC ENGINEERING	TUBING POLYURETHANE NOC
PLASTIC EXTRUSION	TUBING ESTANE
	TUBING SOLPRENE 416
PLASTIC PROFILE	KEL-F CTFE UNPLASTICIZED
PLASTIC TRADING	PLASTIC PLASTAFLEX SCPP2500CB
PLASTICS & TOOLING	MOLD COMPOUND AKEMI #4
PLASTISOL	COATING EVA PATCHES
	INK SILKSCREEN RED
PLAYTEX	TAMPONS DEODORANT SUPER PLUS
PLICON CORPORATION	LAMIN POLYETHYLENE/PLASTIC
PN100-004-233-3099AF	FASTENER VELCRO ASTRO HOOK AND LOOP
PN100-082-233-3099AF	FASTENER VELCRO ASTRO HOOK AND LOOP
PNJT00RP-10-99510051	CONNECTOR ELECTRICAL
PNJT06RP-10-9910051	CONNECTOR ELECTRICAL
POLAROID	FILM PHOTOGRAPHIC 107 B & W
	FILM PHOTOGRAPHIC 667
	FILM POLAROID 3000 LAND TY 107
	FILM POLAROID 669 POLACOLOR ER INSTANT PACK
POLIFIL	PLASTIC POLIFIL C-20
	PLASTIC POLIFIL C-40
	PLASTIC POLIFIL CAS-40
	PLASTIC POLIFIL HM20
	PLASTIC POLIFIL HM40
	PLASTIC POLIFIL M20
	PLASTIC POLIFIL M40
	PLASTIC POLIFIL RMC-20
	PLASTIC POLIFIL RMC-40
	PLASTIC POLIFIL RMT-20
	PLASTIC POLIFIL RMT-40
	PLASTIC POLIFIL T-20
	PLASTIC POLIFIL T-40
POLY SCIENTIFIC	COATING EPOXY/SILICATE 193
	POTTING COMPOUND EPOXY/SILICATE ES180
	POTTING COMPOUND EPOXY/SILICATE ES218
POLY-AMERICA	FILM POLYETHYLENE
POLY-CARB	ADHESIVE MARK 10
	ADHESIVE MARK 10.3
	ADHESIVE MARK 19
	ADHESIVE MARK 231 EPOXY PUTTY
	ADHESIVE MARK 24
	ADHESIVE MARK 25
	ADHESIVE MARK 25.3
	ADHESIVE MARK 29
	ADHESIVE MARK 3
	ADHESIVE MARK 30
	ADHESIVE MARK 30.1
	ADHESIVE MARK 8
POLY-FREEZE	ADHESIVE POLYFREEZE P146 EPOXY
POLYBLEND INC	INSULATION FOAM PBO21-44 POLYURETHANE
POLYFLON CORP	KEL-F 81
	KEL-F CTFE UNPLASTICIZED
POLYGON	MOLD COMPOUND MELAMINE/GLASS GF-5
POLYMER COMPOSITES	PLASTIC HIMOD N66GL40
	PLASTIC HIMOD N66KV20
POLYMER COMPOSITES	PLASTIC HIMOD N6GL40
	PLASTIC HIMOD N6KV20
	PLASTIC HIMOD PCGL40
	PLASTIC HIMOD PETGL40
	PLASTIC HIMOD PETGL55
	PLASTIC HIMOD PPGL50
	PLASTIC HIMOD PUGL40
	PLASTIC HIMOD PUKV20
	RUBBER PUGL40
	RUBBER PUKV20
POLYMER CORP	NYLATRON MOS2 FILLED NYLON
	PLASTIC IPC104
	PLASTIC IPC120
	PLASTIC IPC170
	PLASTIC IPC171E
	PLASTIC IPC173
	PLASTIC IPC176
	PLASTIC IPC1832
	PLASTIC IPC1833
	PLASTIC IPC1834
	PLASTIC IPC1836
	PLASTIC IPC1837
	PLASTIC IPC5007
	PLASTIC IPC5100
	PLASTIC IPC5303
	PLASTIC IPC5304
	PLASTIC IPC5306
	PLASTIC IPC5308
	PLASTIC IPC5800
	PLASTIC IPC6000
	PLASTIC IPC6025
	PLASTIC IPC6045
	PLASTIC IPCPX6000
	PLASTIC IPCPX6030
	PLASTIC IPCRCF3020
	PLASTIC IPCRCF3030
	PLASTIC IPCRCF3040
	PLASTIC IPCRX171E
	PLASTIC IPCRX173
	PLASTIC IPCRX176
	PLASTIC IPCRX1834
	PLASTIC IPCRX5308
	PLASTIC POLYPENCO PTFE FLUOROCARBON
	PLASTIC TORLON 4203
	PLASTIC ULTRA-WEAR UHMUPE
POLYMER DEVELOPMENT	INSULATION FOAM PDL4034 COVERED WITH L-T-80 TAPE AND THEN G401000 TAPE
	INSULATION FOAM PDL4034 FR POLYURETHANE
	INSULATION FOAM PDL4034-2.5 WRAPPED WITH ARAMID SLEEVING/COATED WITH PR1660/SEALED WITH DAPCOSEAL 2030
	INSULATION FOAM PDL4034-2.5S/ENSHROUDED IN METAL FOIL
	INSULATION FOAM PDL4034/COATED WITH FRL
	INSULATION FOAM POLYURETHANE PDL2207

MSFC-HDBK-527 REV F 9999942 0006942 3

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
POLYMER DEVELOPMENT	INSULATION FOAM POLYURETHANE PDLX10-241
	NYLATRON GS/GLASS FILLED NYLON
POLYPENCO	TAPE POLYPENCO 2003 PTFE
	TAPE TFE/SILICONE 503-5-DC ADHESIVE
POLYSAR	PLASTIC POLYSAR 101
	PLASTIC POLYSAR 103
	PLASTIC POLYSAR 200
	PLASTIC POLYSAR 202
	PLASTIC POLYSAR 203
	PLASTIC POLYSAR 205
	PLASTIC POLYSAR 208
	PLASTIC POLYSAR 220
	PLASTIC POLYSAR 2220
	PLASTIC POLYSAR 2400
	PLASTIC POLYSAR 3350
	PLASTIC POLYSAR 415
	PLASTIC POLYSAR 4220
	PLASTIC POLYSAR 4300
	PLASTIC POLYSAR 520
	PLASTIC POLYSAR 5220
	PLASTIC POLYSAR 525
	PLASTIC POLYSAR 555
	PLASTIC POLYSAR 777
	PLASTIC POLYSAR 9720
PORT PLASTICS	KEL-F 81
	NYLON 6/6
	PLASTIC RULON A TFE/GLASS
	TEFLON TFE VIRGIN
PORTER SEAL	RUBBER VITON FLUID RESISTANT
POTTER CORP	BEADS GLASS SODALIME TY SILICA
POWER SYSTEMS	RUBBER BUTYL R/S 201-6
PPG INDUSTRIES	COATING PRIMER POLYCLUTCH
	PLASTIC CR39
	PLASTIC HIRI 2 CASTING RESIN (EXTRA)
	PLASTIC HIRI 2 CASTING RESIN (NON-FLAMMABLE)
PPL-3226-78/8-79091	INSULATION FOAM NOPCO G306R/G306T
PRATT & LAMBERT	COATING KP420/6383
PRECISION ASSOCIATES	RUBBER VITON 8846
PRECISION CONNECTORS	CONN TERMINAL FUNCTION MODULES
PRECISION RUBBER	RUBBER EPR 3177
	RUBBER FLUOROELASTOMER O-RING
	RUBBER FLUOROSILICONE
	RUBBER NITRILE CPD 7377
	RUBBER SILICONE 11307
	RUBBER SILICONE PRP11207
	RUBBER VITON 19357
PRECISION TUBE	TUBING THINWALL P100 SQUARE FORM SPIRAL WRAPPED
PREECE INC	TUBING NOMEX/TEFLON/SILICONE
PREFORM INC	FABRIC KELVAR 29
PREMIER	CORD DACRON 3
	THREAD DACRON "B"
	THREAD DACRON "FF"
	THREAD KEVLAR SIZE E

MANUFACTURER	DESIGNATION
PREMIX INC	MOLD COMPOUND BMC-15 6100 POLYES/GL
	MOLD COMPOUND POLYES/GL G100 BMC-LS
	PLASTIC POLYSTYROL 158K
	PLASTIC PREMIGLAS 1000 BMC GLASS
	PLASTIC PREMIGLAS 1100 BMC LS 15% GLASS
	PLASTIC PREMIGLAS 1100 BMC-LS 22% GLASS
	PLASTIC PREMIGLAS 1100 BMC-LS 30%GLAS
	PLASTIC PREMIGLAS 1100-05
	PLASTIC PREMIGLAS 1100-10
	PLASTIC PREMIGLAS 1100-15
	PLASTIC PREMIGLAS 1200 SMC-LS 15% GLASS
	PLASTIC PREMIGLAS 1200 SMC-LS 22% GLASS
	PLASTIC PREMIGLAS 1200 SMC-LS 30% GLASS
	PLASTIC PREMIGLAS 2000 BMC 10% GLASS
	PLASTIC PREMIGLAS 2000 BMC 15% GLASS
	PLASTIC PREMIGLAS 2000 BMC 22% GLASS
	PLASTIC PREMIGLAS 2000 BMC 30% GLASS
	PLASTIC PREMIGLAS 2003 22% GLASS
	PLASTIC PREMIGLAS 2003 BMC 15% GLASS
	PLASTIC PREMIGLAS 2003 BMC 30% GLASS
	PLASTIC PREMIGLAS 2100 BMC-LS 15% GLASS
	PLASTIC PREMIGLAS 2100 BMC-LS 22% GLASS
	PLASTIC PREMIGLAS 2100 BMC-LS 30% GLASS
	PLASTIC PREMIGLAS 2103 BMC-LS 15% GLASS
	PLASTIC PREMIGLAS 2103 BMC-LS 22% GLASS
	PLASTIC PREMIGLAS 2103 BMC-LS 30% GLASS
	PLASTIC PREMIGLAS 2200 SMC-LS 15% GLASS
	PLASTIC PREMIGLAS 2200 SMC-LS 22% GLASS
	PLASTIC PREMIGLAS 2200 SMC-LS 30% GLASS
	PLASTIC PREMIGLAS 2203 SMC-LS 15% GLASS
	PLASTIC PREMIGLAS 2203 SMC-LS 22% GLASS
	PLASTIC PREMIGLAS 2203 SMC-LS 30% GLASS
	PLASTIC PREMIGLAS 3000 BMC 15% GLASS
	PLASTIC PREMIGLAS 3000 BMC 30% GLASS
	PLASTIC PREMIGLAS 3100 BMC-LS 15% GLASS
	PLASTIC PREMIGLAS 3100 BMC-LS 22% GLASS
	PLASTIC PREMIGLAS 3100 BMC-LS 30% GLASS
	PLASTIC PREMIGLAS 3140 MSG
	PLASTIC PREMIGLAS 3200 SMC-LS 15% GLASS
	PLASTIC PREMIGLAS 3200 SMC-LS 22% GLASS
	PLASTIC PREMIGLAS 3200 SMC-LS 30% GLASS
	PLASTIC PREMIGLAS 4000 BMC 15% GLASS
	PLASTIC PREMIGLAS 4000 BMC 22% GLASS
	PLASTIC PREMIGLAS 4000 BMC 30% GLASS
	PLASTIC PREMIGLAS 4100 BMC-LS 22% GLASS
	PLASTIC PREMIGLAS 4100 BMC-LS 30% GLASS
	PLASTIC PREMIGLAS 4200 SMC-LS 15% GLASS
	PLASTIC PREMIGLAS 4200 SMC-LS 22% GLASS
	PLASTIC PREMIGLAS 4200 SMC-LS 30% GLASS
	PLASTIC PREMIGLAS 7100 BMC 15% GLASS
	PLASTIC PREMIGLAS 7100 BMC 22% GLASS
	PLASTIC PREMIGLAS 7200 SMC
	PLASTIC PREMIGLAS 7200 SMC 15% GLASS
	PLASTIC PREMIGLAS 7200 SMC 22% GLASS
	PLASTIC PREMIGLAS 7200 SMC 30% GLASS

MSFC-HDBK-527 REV F 9999942 0006943 5

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
PREMIX INC	PLASTIC PREMIGLAS 8140 TMC
	PLASTIC PREMIGLAS 8200 SMC
	PLASTIC PREMIGLAS BMC-EMI
	PLASTIC PREMIGLAS BMC-ESD
	PLASTIC PREMIGLAS EPOXY 1200E 50% GLASS
	PLASTIC PREMIGLAS EPOXY 1200E 65% GLASS
	PLASTIC PREMIGLAS HSMC
	PLASTIC PREMIGLAS HSMC 3200 50% GLASS
	PLASTIC PREMIGLAS SMC-EMI
	PLASTIC PREMIGLAS SMC-ESD
	PLASTIC PREMIGLAS TMC-EMI
	PLASTIC PREMIGLAS TWC-ESD
	PLASTIC PREMIJECT 1100V BMC-LS
	PLASTIC PREMIJECT 1140 TMC-LS
	PLASTIC PREMIJECT 1140V TMC-LS
	PLASTIC PREMIJECT 6000 BMC 10% GLASS
	PLASTIC PREMIJECT 6000 BMC 15% GLASS
	PLASTIC PREMIJECT 6000 BMC 20% GLASS
	PLASTIC PREMIJECT 6000 BMC 5% GLASS
	PLASTIC PREMIJECT 6100 BMC-LS 10% GLASS
	PLASTIC PREMIJECT 6100 BMC-LS 15% GLASS
	PLASTIC PREMIJECT 6100 BMC-LS 20% GLASS
	PLASTIC PREMIJECT 6100 BMC-LS 5% GLASS
PRESERVO PAINT	COATING POLYTHANE CP500 SERIES/VINYL
	PHENOLIC VPP-702 PRIMER
PRESTO	INSULATION FOAM PYRELL/PRESTO 765/UT
	INSULATION FOAM PYRELL/PRESTO P/6
PRESTOLITE	WIRE ELEC ETFE TEFZEL
PRIMER/DESOTO	COATING 03-BK-29 PRIMER
	COATING 03-GY-62 GRAY OVER MB0125-055
	PRIMER
	COATING 03-Y-30 PRIMER
PRINCE MATCHABELLI	MASCARA EXTRA LNGTH WITH SEALER
PRO DISPOSABLES	PAD PREP PROVIDINE-IODINE
PROCTER & GAMBLE	TOOTHPASTE CREST
PROD RESEARCH & CHEM	ADHESIVE 444R
	ADHESIVE 898C
	ADHESIVE P/S 700
	ADHESIVE P/S 706A
	ADHESIVE P/S 706B1/2
	ADHESIVE P/S 706B2
	ADHESIVE P/S 714
	ADHESIVE P/S 870-2
	ADHESIVE P/S 870A1/2
	ADHESIVE P/S 870A2
	ADHESIVE P/S 870B1/2
	ADHESIVE P/S 870C
	ADHESIVE P/S 870C12
	ADHESIVE P/S 870C24
	ADHESIVE P/S 872B1/2
	ADHESIVE P/S 872B2
	ADHESIVE P/S 881-1/6
	ADHESIVE P/S 888-2
	ADHESIVE P/S 888D1/2
	ADHESIVE P/S 890A1/2

MANUFACTURER	DESIGNATION
PROD RESEARCH & CHEM	ADHESIVE P/S 890A2
	ADHESIVE P/S 890B1/2
	ADHESIVE P/S 890B4
	ADHESIVE P/S 898B8
	ADHESIVE P/S 898D2
	ADHESIVE P/S 899A1/2
	ADHESIVE P/S 899A2
	ADHESIVE P/S 899B1/2
	ADHESIVE P/S 899B1/4
	ADHESIVE P/S 899B2
	ADHESIVE P/S 899B4
	ADHESIVE P/S 899B6
	ADHESIVE POLYSULFIDE PR14600
	ADHESIVE PR1221 CLASS A
	ADHESIVE PR1321 CLASS A
	ADHESIVE PR1403G A-1/2
	ADHESIVE PR1403G A-2
	ADHESIVE PR1403G B-1/2
	ADHESIVE PR1403G B-2
	ADHESIVE PR1422A1/2
	ADHESIVE PR1422A2
	ADHESIVE PR1422B1/2
	ADHESIVE PR1422B2
	ADHESIVE PR1422G B1/2
	ADHESIVE PR1422G B2
	ADHESIVE PR1425B1/2
	ADHESIVE PR1425B2
	ADHESIVE PR1426
	ADHESIVE PR1431G T2
	ADHESIVE PR1431G T3
	ADHESIVE PR1431G T4
	ADHESIVE PR1431G TI
	ADHESIVE PR1435
	ADHESIVE PR1435G
	ADHESIVE PR1436G A1/2
	ADHESIVE PR1436G A2
	ADHESIVE PR1436G B2
	ADHESIVE PR1436G B4
	ADHESIVE PR1436G SPRAYABLE
	ADHESIVE PR1440A1/2
	ADHESIVE PR1440A2
	ADHESIVE PR1440B1/2
	ADHESIVE PR1440B2
	ADHESIVE PR1440C2
	ADHESIVE PR1440C20
	ADHESIVE PR1546L
	ADHESIVE PR1590
	ADHESIVE PR1710
	ADHESIVE PR1710-1711 VITON
	ADHESIVE PR1725B2
	ADHESIVE PR175082 POLYSULFIDE
	ADHESIVE PR1750A-2
	ADHESIVE PR1750A1/2
	ADHESIVE PR1755
	ADHESIVE PR2701

MSFC-HDBK-527 REV F 9999942 0006944 7

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
PROD RESEARCH & CHEM	ADHESIVE PR2702
	ADHESIVE PR2751
	ADHESIVE PR2752
	ADHESIVE PR380
	ADHESIVE PR383
	ADHESIVE PR702
	ADHESIVE PR703
	ADHESIVE PR810
	ADHESIVE PR812
	ADHESIVE PR927
	ADHESIVE PR938
	ADHESIVE PR957
	COATING CARBOLINE NO 30 SEE RPT
	COATING POLYURETHANE PR1060D
	COATING POLYURETHANE PR1120
	COATING POLYURETHANE PR1506
	COATING POLYURETHANE PR1535
	COATING POLYURETHANE PR1546
	COATING POLYURETHANE PR1564
	COATING POLYURETHANE PR1568 CONFORMAL
	COATING POLYURETHANE PR1568M
	COATING POLYURETHANE PR1654
	COATING POLYURETHANE PR420
	COATING PR484TC/PR475S/PR19 PR
	COATING PRC NO 1 SEE TEST REPORT
	COATING PRC NO 2 SEE TEST REPORT
	COATING PRC NO 21 SEE TEST RPT
	COATING PRC NO 3 SEE TEST REPORT
	COATING PRC NO 4 SEE TEST REPORT
	COATING PRC NO 5 SEE TEST REPORT
	COATING PRC NO 6 SEE TEST REPORT
	COATING PRC NO 7 SEE TEST REPORT
	COATING PRC NO 8 SEE TEST RPT
	COATING PRC NO 9 SEE TEST RPT
	COATING PRC22 SEE TEST REPORT
	COATING PRC23 SEE TEST REPORT
	COATING PRC24 SEE TEST REPORT
	COATING PRC25 SEE TEST REPORT
	COATING PRC26 SEE TEST REPORT
	COATING PRC27 SEE TEST REPORT
	COATING PRC28 SEE TEST REPORT
	COATING PRC29 SEE TEST REPORT
	POTTING COMPOUND POLYURETHANE PRP1538
	POTTING COMPOUND PR1547 BLACK POLYURETHANE
	POTTING COMPOUND PR1578 POLYURETHANE
	RUBBER NEOPRENE PRP2337
	RUBBER SILICONE RTV 855
	SEALANT CYANOSILICONE PRP711
	SEALANT POLYSULFIDE 1221B-2
	SEALANT POLYSULFIDE PR1201 RLS
	SEALANT POLYSULFIDE PR1201HT
	SEALANT POLYSULFIDE PR1422
	SEALANT POLYSULFIDE PR1750B
	SEALANT POLYSULFIDE PR1770
	SEALANT POLYSULFIDE PR1770 FR
PROD RESEARCH & CHEM	SEALANT POLYSULFIDE PR385M
	SEALANT POLYSULFIDE PRP1436
	SEALANT POLYURETHANE PR1656
	SEALANT POLYURETHANE PR1660
	SEALANT POLYURETHANE PRP1600
	SPONGE RUBBER SILICONE PR855 FR
PROD TECHNIQUES	COATING PT111 LACQUER
	COATING PT401 RESIN
	COATING PT401 RESIN/PT402 PRIMER
	COATING PT404A
	COATING PT750/PT402 PRIMER
	COATING SILICONE WHITE PT805
	TRANSITE PT401 COATED
PRODESCO	FABRIC FIBERGLASS 1450-045
	FABRIC KEVLAR 29/H7000-605
	FABRIC KEVLAR 9M03893/1813
	FABRIC KEVLAR GAC-RF443
	FABRIC PAN 2700-40
	FABRIC TEFLON T9362/TFE COATED
PROTECTIVE LINING	FILM POLYETHYLENE
PROTOTYPE & PLASTICS	MOLD COMPOUND ETHYLENE VINYL ACETAT
PT A:1017&PT B:1025	POTTING COMPOUND SCOTCHCAST 247
PTIZER	ALCOHOL WIPES HRI8026-4204-0
PTK CORP	POTTING COMPOUND SIL PTK 16000-002
PURAFIL INC	PURAFIL AL203/KMN04 INORGANIC
PURE CARBON	ADHESIVE PUREBOND P658RC
	SEALANT CARBON PLUS BINDER P4229
PUREX CORP	CORK P50/COATING TURCO T6109
PUTNAM MILLS	FABRIC NOMEX TWILL POLYI
PYLE NATIONAL CO	COMPOUND E4-7.25 GLASS FILLED/GREEN
	COMPOUND E4-7.68/GLASS/DARK GREY
	COMPOUND E4-7.70 GLASS FILLED/BLACK
	COMPOUND E4-7.71 GLASS FILLED/BLACK
	COMPOUND E4-8.97 BLUE
PYROTRONICS	MOLD COMPOUND MACROLON 3000
QPL	CLAMP NEOPRENE/AL MS21919DG
	FABRIC RTV E 1581 GLASS
	FILTER TYPE G THICKNESS G-0110
	RUBBER BUNA N
QSL	FABRIC NYLON
	FELT NOMEX/DC92-007 SILICONE COATED
	RUBBER VITON FLUID RESISTANT
	WEBBING NOMEX 14.4OZ
	WEBBING NOMEX 22.4OZ
	WIRE ELEC TFE/ML ENAMEL
QSL/MOHAWK MILLS	FABRIC SILICONE RUBBER/ARAMID
QUAKER STATE	LUBE OIL QUAKER STATE 90
QUICK-TAPE SALES CO	TAPE FIBERGLASS QUIK-TAPE
QUINTEC INDUSTRIES	TUBING TEFLON FEP HST
QUIRK WIRE CO	CABLE ELEC PTFE WITH SHEATH TAPE
	CABLE ELEC TFE/BEN-HAR SLEEVE
	CABLE ELEC TFE/VARGLAS SLEEVE
R E DARLING	HOSE REDAR A111331-1 VITON B
	HOSE REDAR A11200 SILICONE/PBI
	HOSE REDAR SI644-01 SILICONE

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
R E DARLING	HOSE URINAL SILICONE RUBBER/WIRE
	HOSE WAVA SILICONE/NOMEX
	TUBING FLUOREL 50FC009
R E I	PLASTIC MINI-TOGGLE ABS
R F CARLSON	RUBBER VITON CPD 68514A
R O HULL	COATING PHENOLIC BASE
R S HUGES COMPANY	TAPE SCOTCHMOUNT 4032
R T VANDERBILT	ADHESIVE VANCHEM HM50
R W ELDRIDGE CO	FABRIC COTTON HANDKERCHIEF
RANDOLPH PRODUCTS	COATING 33798 TOPCOAT WITH POLYAMIDE PRIMER
	COATING EPOXY POLYAMIDE RED 11105
	COATING YELLOW 33798 PRIMER/EPOXY TOPCOAT
	SEALANT ZINC CHROMATE GRAY
RANGER WIRE & CABLE	WIRE ELEC FEP
RAYBESTOS-MANHATTAN	ADHESIVE 84706
	BRAKE MATERIAL M4952
	BRAKE MATERIAL R740 BTG
	BRAKE MATERIAL S1698-5
	BRAKE MATERIAL S451
	CLAMP RL5033/CUSHION L32171
	COATING REFSET
	COATING REFSET L3203-6
	COATING REFSET RL4389
	COATING REFSET RL4389 CRYO-INSULATION
	FABRIC FLUOREL/GLASS RL3520
	FABRIC PHENOLIC/RESIN R1492Y12
	FLUOROCARBON RL-3540 GUM STOCK
	INSULATION FOAM CPR306-2/REFSET COATED
	INSULATION FOAM FLUOREL G306/L3203-6
	INSULATION FOAM FLUOREL/URETHANE COATED
	INSULATION FOAM PYRELL/REFSET RL4389 COATED
	INSULATION FOAM SILICONE RL1973
	INSULATION POLYSTYRENE/FLUOREL
	LAMIN ASBESTOS/FIBERGLASS RVV647F
	RUBBER FLUOREL 2231
	RUBBER FLUOREL 3217
	RUBBER FLUOREL 5033
	RUBBER FLUOREL 5767-1
	RUBBER FLUOREL 5823
	SPONGE FLUOREL RL 4714
	SPONGE FLUOREL RL2060
	SPONGE FLUOROELASTOMER R1M693
	TAPE STRETCH RL6000SA
	WEBBING FLUOREL GLASS RL 3603
RAYCHEM	RUBBER SILICONE NOC
RAYCHEM CORP	ADHESIVE S1006
	ADHESIVE S1010
	ADHESIVE S1125
	CABLE COAXIAL 26 AWG
	CABLE FIBER OPTIC VSC-A1-10-17
	CONFIG VITON RT876/THERMOFIT
	FABRIC STILAN 541 WOVEN
	HARNESS AND CONNECTOR 26 AWG

MANUFACTURER	DESIGNATION
RAYCHEM CORP	INK TMS ON KYNAR/VITON SHEETS
	KYNAR MELTABLE PIGMENTED BLUE
	KYNAR MELTABLE PIGMENTED RED
	KYNAR MELTABLE PIGMENTED YELLOW
	LABELS THERMOFIT SLIP-ON HT TMS CM
	LABELS THERMOFIT TIE-ON HT TMS CM
	MARKER CABLE HT-TMS-CM
	MARKER SLEEVE KYNAR THERMOFIT
	MARKER SLEEVING HT-TMS KYNAR/VITON HS
	SOLDER SLEEVE D101-00
	TUBING FP301 TYPE 2 POLYOLEFIN HS
	TUBING HS RT 1312 VITON
	TUBING KYNAR 01744-08 SOLDER SLEEVE
	TUBING KYNAR CONVOLUTED BLACK
	TUBING KYNAR RT1150 CONVOLUTED
	TUBING KYNAR RT850 HST
	TUBING NEOPRENE RT510 HST
	TUBING POLYCHLOROPRENE HST
	TUBING POLYOLEFIN DUAL WALL HST
	TUBING POLYOLEFIN RNF100
	TUBING POLYOLEFIN RT102 HST
	TUBING POLYOLEFIN RT1304 HST
	TUBING POLYOLEFIN RT301/S1024
	TUBING POLYOLEFIN RT360 TYPE 2
	TUBING POLYOLEFIN RT876 HST
	TUBING POLYOLEFIN TAT125 HST
	TUBING POLYVINYLFLOURIDE K46 HS
	TUBING THERMOFIT 218 HST CONVLEX
	TUBING THERMOFIT 222D242 HS
	TUBING THERMOFIT 222D253 HS
	TUBING THERMOFIT HS
	TUBING THERMOFIT RT218
	TUBING THERMOFIT S1009 EPOXY
	TUBING THERMOFIT S1017
	TUBING THERMOFIT S1044 VITON
	TUBING THERMOFIT VITON HST
	TUBING VITON HST
	TUBING VITON RT1146 HST
	WIRE ELEC ETFE TEFZEL
	WIRE ELEC FEP WITH POLYIMIDE TAPE
	WIRE ELEC KAPTON TAPE/GLASS TUBE
	WIRE ELEC KYNAR PVF
	WIRE ELEC POLYIMIDE/KYNAR RT850
	WIRE ELEC PVC
	WIRE ELEC RAYCHEM 44 ALL GAGES
	WIRE ELEC RAYCHEM 44 BETAWRAP
	WIRE ELEC RAYCHEM 44 FABRIC/MESH
	WIRE ELEC RAYCHEM 44 MYLAR/KAPTON
	WIRE ELEC RAYCHEM 44 SHIELD/INSULATION
	WIRE ELEC RAYCHEM 44 WITH ATLAS TUBE
	WIRE ELEC RAYCHEM 44 WITH FEP TUBING
	WIRE ELEC RAYCHEM 44/KAPTON
	WIRE ELEC RAYCHEM 55 ETFE
	WIRE ELEC RAYCHEM CU/MYLAR/KAPTON
	WIRE ELEC TEFLON TFE

MSFC-HDBK-527 REV F ■ 9999942 0006946 0 ■

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
RAYCHEM CORP	WIRE ELEC TRIAXIAL
	WIRE ELEC WITH FIBERGLASS SLEEVE
	WIRE ELEC WITH METAL BRAID SHIELD
RAYMARK INDUSTRIAL DIVISION	ADHESIVE R81005
	ADHESIVE R81007
	ADHESIVE R81012
	ADHESIVE R81816
	ADHESIVE R82007
	ADHESIVE R82016
	ADHESIVE R84017
	ADHESIVE R84025
	ADHESIVE R84048
	ADHESIVE R84067
	ADHESIVE R85013
	ADHESIVE RAYBOND R85014
	ADHESIVE RAYBOND R86009
	ADHESIVE RAYBOND R86025
RAYOVAC CORP	BATTERY RAYOVAC ALKALINE SIZE AA
RCA	FILM RCA
	LAMIN EPOXY/GLASS 185206
	RUBBER SILASTIC E RTV SILICONE
	TAPE KAPTON/DACRON/CHEMGLAZE
	WIRE ELEC SILICONE RUBBER 20 AWG
RE CORP	PLASTIC RTP 200H FR
RECTICEL FOAM CORP	FILM VINYL COTTON TEXLE BACKED
REEVES BROS	FABRIC 100% COTTON FR 7 OZ BLUE
	FABRIC ALUMINIZED DS662 POLYURETHANE POLYESTER COATED
	FABRIC ALUMINIZED NS458 POLYURETHANE COATED NYLON
	FABRIC BIAS PLY COATED
	FABRIC COTTON 100%(FR/2%THPOH)
	FABRIC COTTON FLAME RETARDANT
	FABRIC FR COTTON 7 OZ/SQ YD
	FABRIC M11673 ALUMINIZED POLYURETHANE COATED NYLON
	FABRIC NYLON URETHANE-CARBON IMPREGNATED COATED
	INSULATION FOAM GRADE 1331
REISS INDUSTRIES	INSULATION FOAM MOLECULON RP11 URETHANE
RELIABLE MFG	ADHESIVE RELIABOND 382 EPOXY FILM
	ADHESIVE RELIABOND 398 EPOXY FILM
	ADHESIVE RELIABOND 7115 EPOXYFILM
REMINGTON	RAZOR RECHARGEABLE XLR900
	RAZOR XLR500
REMTEK CORP	TUBING FP301 TYPE 2 POLYOLEFIN HS
	TUBING FRC125 HST
	TUBING KYNAR PVF175 HS
	TUBING NT120 NEOPRENE HST
	TUBING POLYOLEFIN DWP125
	TUBING POLYOLEFIN GPO135 BLK
	TUBING POLYOLEFIN GPO135 T2
	TUBING POLYOLEFIN GPR135 BLK
	TUBING POLYOLEFIN RET125 HST
	TUBING POLYOLEFIN RTA125 HST

MANUFACTURER	DESIGNATION
REMTEK CORP	TUBING TEKFIT A222003 HS BLACK
REN PLASTICS	ADHESIVE URETHANE RP6401
	LAMIN EPOXY/GLASS AEROLAM 110/RP57
	POTTING COMPOUND POLYURETHANE DC902-1
REPUBLIC PACKAGING	INSULATION FOAM LS645C2
	INSULATION FOAM MINICELL L200/AL 5052H32
	INSULATION FOAM MINICELL L200/FLUOREL
	INSULATION FOAM URETHANE BLACK
	INSULATION FOAM URETHANE L200
	INSULATION FOAM URETHANE/ARMALON/CSR300 ADHESIVE
REPUBLIC PACKAGING/	INSULATION FOAM MINICELL L200/REFSET RL
RAYBESTOS-MANHATTAN	4389 COATING
REPUBLIC RUBBER PROD	SPONGE RUBBER NEOPRENE STY36-2V 40LB
RESART	COATING SF-X-HARDCOAT ANTISCRATCH
RESEARCH CHEMICAL	POTTING COMPOUND PR1201Q
RESEARCH PRODUCTS	WEBBING NYLON/NEOPRENE 3090
RESINOID ENGINEERING	PLASTIC RESINOID 1312
	PLASTIC RESINOID 1320
	PLASTIC RESINOID 1321
	PLASTIC RESINOID 1322
	PLASTIC RESINOID 1323
	PLASTIC RESINOID 1324
	PLASTIC RESINOID 1325
	PLASTIC RESINOID 1340
	PLASTIC RESINOID 1360
	PLASTIC RESINOID 1362
	PLASTIC RESINOID 1370
	PLASTIC RESINOID 1401
	PLASTIC RESINOID 1402
	PLASTIC RESINOID 2002-2
	PLASTIC RESINOID 2002-4
	PLASTIC RESINOID 2002-4P
	PLASTIC RESINOID 2002C5
	PLASTIC RESINOID 2016
	PLASTIC RESINOID 2017
	PLASTIC RESINOID 2018
	PLASTIC RESINOID 7003S
	PLASTIC RESINOID 7005
	PLASTIC RESINOID 7051
	PLASTIC RESINOID 7051SS
	PLASTIC RESINOID 7201
	PLASTICS RESINOID 2010
RESISTOFLEX CO	HOSE FLEX PTFE/CARBON FILLED
	HOSE FLEX R19840X-032L
	HOSE FLUOROFLEX-T
	HOSE FLUOROFLEX-T T1000
	HOSE LINER PTFE
	HOSE LINER/R762-8 HOSE
	HOSE NYLON/TEFLON R531-4
	HOSE R502-16Z TEFLON
	HOSE R502-6 TEFLON
	HOSE R502-8 TEFLON
	HOSE TEFLON PTFE R735
	HOSE TEFLON PTFE R765

MSFC-HDBK-527 REV F 9999942 0006947 2

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
RESISTOFLEX CO	HOSE TEFLON T6C
	HOSE TEFLON TFE R736
	TEFLON TFE VIRGIN
REVLON	DEODORANT MITCHUM STICK
	EYE COLOR FROST FORMULA 2
	EYE COLOR STICK PROFESSIONAL
	EYE LINER
	EYE MAKEUP REMOVER 30 SEC
	EYE SHADOW CREAM-ON SUPER LUST
	LIPSTICK NATURAL WONDER
	MAKEUP CHEEKCOLOR POWDER
	MASCARA SUPER RICH
REXHAM-INDUSTRIAL FILM DIV.	FILM MYLAR SHEET/POLLOK LOCKING ELEMENT GREEN
REYNOLDS	WIRE ELEC TEFLON TFE
RHONE-POULENC	PLASTIC KINEL 3515
	PLASTIC KINEL 4515
	PLASTIC KINEL 5504
	PLASTIC KINEL 5505
	PLASTIC KINEL 5508
	PLASTIC KINEL 5511
	PLASTIC KINEL 5514
	PLASTIC KINEL 5517
	PLASTIC KINEL 5518
	PLASTIC TECHNYL A20
	PLASTIC TECHNYL A20 V25
	PLASTIC TECHNYL A216
	PLASTIC TECHNYL A216 V10
	PLASTIC TECHNYL A216 V15
	PLASTIC TECHNYL A216 V20
	PLASTIC TECHNYL A216 V25
	PLASTIC TECHNYL A216 V30
	PLASTIC TECHNYL A216 V35
	PLASTIC TECHNYL A216 V40
	PLASTIC TECHNYL A216 V50
	PLASTIC TECHNYL A217
	PLASTIC TECHNYL A218
	PLASTIC TECHNYL A218 V20
	PLASTIC TECHNYL A218 V25
	PLASTIC TECHNYL A218 V30
	PLASTIC TECHNYL A218 V40
	PLASTIC TECHNYL A221
	PLASTIC TECHNYL A222
	PLASTIC TECHNYL A228 MT40
	PLASTIC TECHNYL A248 MT30
	PLASTIC TECHNYL A319
	PLASTIC TECHNYL B216
	PLASTIC TECHNYL B216 V20
	PLASTIC TECHNYL B216 V30
	PLASTIC TECHNYL B216 V50
	PLASTIC TECHNYL B217
	PLASTIC TECHNYL B218
	PLASTIC TECHNYL B218 MX30
	PLASTIC TECHNYL B218 MX40
	PLASTIC TECHNYL B230
RHONE-POULENC	PLASTIC TECHNYL C216
	PLASTIC TECHNYL C216 V20
	PLASTIC TECHNYL C216 V30
	PLASTIC TECHNYL C316
	PLASTIC TECHNYL D316
	PLASTIC TECHNYL D317
RICHARDSON CO	FABRIC NYLON DACRON COATED
RICHMOND	FILM HS6262 VAC PAK NYLON
	FILM HS800 VAC PAK NYLON GOLD
	FILM HS8171 VAC PAK NYLON
	FILM NYLON CLEAR 06
	FILM NYLON RCAS 2400 ORANGE
	PLASTIC DUOGARD
	PLASTIC RCAS 0600
	PLASTIC RCAS 1200
	PLASTIC RCAS 2400/ANTISTATIC 2 MIL THICK ROLLED INTO TUBULAR SHAPE
	PLASTIC RCAS 3600
	PLASTIC RCAS 4200
RM ENGINEERED PRODUCTS	TAPE RL2168A ASBESTOS COATED WITH BUTYL RUBBER
RM INDUSTRIAL PRODUCTS	RUBBER EP6923
	RUBBER RM630
RM INDUSTRIES	LAMIN EPOXY/GLASS/RL4389 COATED
ROBERTSHAW	ADHESIVE RESIWELD 4 EPOXY
	RUBBER SILICONE S59
	RUBBER SILICONE S64
	RUBBER SILICONE S66
	RUBBER SILICONE SE550
ROCKELL	PLASTIC PENTON
ROCKET CHEM	COATING WD40
ROCKETDYNE	FABRIC RTV E 1581 GLASS
	PLATING GOLD ON A-286
ROCKWELL	CABLE CLAMP ME 127-0071
	CABLE CRES LUBRICATED
	CERAMIC AB312 FABRIC/ACRYLIC/FC723
	CERAMIC AB312 FABRIC/POLYSULFONE/FC723
	COATING MOIST BARRIER SIM-HRSI
	COATING MOIST BARRIER SIM-LRSI
	COATING SILICONE BLACK
	COMPOUND ANTI-ICING DMSO/H20/PECTIN
	CURTAIN HYGIENE CLOSURE
	DISC AL LITHIUM ALLOY
	FABRIC 7878 FIRE/WATER PROOF
	FABRIC CERAMIC AB312 SILICONE COATED
	FABRIC GAP FILLER
	FABRIC NOMEX 7878/POLYESTER954
	FABRIC NOMEX-BLUE WITH FC4101-C16
	FELT NOMEX/SILICONE COATED
	INSULATION FOAM EPOXY SYNTACTIC MODIFIED
	INSULATION FOAM POLYURETHANE/FABRIC/REFSET COAT
	INSULATION FOAM POLYURETHANE/TAPE AL 425
	INSULATION FOAM POLYURETHANE/TAPE AL 7402
	INSULATION FOAM/KEVLAR PR1660/SEAL 2030

MSFC-HDBK-527 REV F 9999942 0006948 4

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
ROCKWELL	LAMIN EPOXY/GRAPHITE HMFB3-714H
	LAMIN EPOXY/KEVLAR DUCT
	LAMIN F164/181 KEVLAR-49
	LAMIN KEVLAR/PR1660/10% PHOSGRD
	LAMIN THORNEL 300/934 GRAPHITE/EPOXY
	MULTI-LAYERED INSULATION ALUMINIZED FIBERGLASS/FEP TEFLON TAPE/SILVER/INCONEL/ POLYESTER
	MULTI-LAYERED INSULATION BLANKET
	MULTI-LAYERED INSULATION DACRON NET B4A/ ALUMINUZED KAPTON/PBI/ALUMINIZED KAPTON RIPSTOP
	MULTI-LAYERED INSULATION DACRON NET B4A/ GOLDIZED KAPTON/TG15000 SILICONE GLASS/ G411660
	MULTI-LAYERED INSULATION DACRON NET B4A/ KAPTON/ALUMINUM/PBI
	MULTI-LAYERED INSULATION DACRON NET B4A/ POLYBENZIMIDAZOLE/TG15000 SILICONE GLASS/ TAPE G411970 ALUMINUM/KAPTON ADHESIVE
	MULTI-LAYERED INSULATION DACRON NET B4A/ TG15000 SILICONE GLASS/KAPTON/PBI
	MULTI-LAYERED INSULATION GOLDIZED KAPTON/ MYLAR
	MULTI-LAYERED INSULATION GOLDIZED KAPTON/ MYLAR/DACRON
	MULTI-LAYERED INSULATION KAPTON AU OUTER KAPTON AL
	MULTI-LAYERED INSULATION KAPTON/ALUMINUM/ TG15000 SILICONE GLASS/DACRON NET B4A/PBI
	MULTI-LAYERED INSULATION KAPTON/BETA
	MULTI-LAYERED INSULATION KAPTON/NOMEX/AU/ TG 15000
	MULTI-LAYERED INSULATION VT70-060065 AL/ POLYIMIDE
	ORBITER RADIATOR COVER
	PANEL GL HONEYCOMB
	RUBBER SILICONE CL 1A & 1B GR 40
	RUBBER SILICONE RTV 560 EPOXY/GLASS
	SILICON CARBIDE DISCONT ON AL
	SILICON CARBIDE ON AL 6061
	STRAP GROUNDING TCS NOMEX/KAPTON
	TUBING KYNAR CONVOLUTED/SS COVR
	WIRE ELEC TEFLON TFE
	Z CONFIG ACCEPTION
	ZIPPER NOMEX/BRASS FIRE/WATER PROOF
ROCOL LIMITED	LUBE OIL KILOPOISE
ROGERS CORP	ELECTRICAL CONNECTOR WITH MOLD COMPOUND RX660
	ENVEX 100 POLYIMIDE
	ENVEX 1000 POLYIMIDE
	ENVEX 1115 POLYIMIDE
	ENVEX 1228 POLYIMIDE/PTFE
	ENVEX 1330 POLYIMIDE/GRAPHITE
	INSULATION FOAM URETHANE PORON CELLULAR FR
ROGERS CORP	LAMIN DUROID BOARD 6006
	LAMIN DUROID BOARD 6010
	LUBE COMPOSITE DUROID 5813
	LUBE COMPOSITE FEURALON AW
	MOLD COMPOUND RX 3-1-530
	OAK BOARD UNCOATED
	PLASTIC ENVEX 1315
	TEFLON DUROID RT4000 AL
	TETRA-ETCH FLUOROCARBON
ROHM & HAAS	LAMIN KYDEX ACRYLIC/PVC ALLOY
	MERLON M-50U POLYCARBONATE
	PLASTIC PLEXIGLASS 2 UVA
	PLASTIC PLEXIGLASS 2-UVT
	PLASTIC PLEXIGLASS 55
	PLASTIC PLEXIGLASS DR100
	PLASTIC PLEXIGLASS G-UVT
	PLASTIC PLEXIGLASS GM2064 GRAY
	PLASTIC PLEXIGLASS MC
	PLASTIC TIFFAK A
	TUBING ACRYLIC RIGID
	TUFFAK POLYCARBONATE F1
ROSCO LAB	FILM ROSCOLUX 51/SUPRISE PINK COLOR FILTER
	FILM ROSCOLUX 88/LIGHT GREEN COLOR FILTER
ROTOTRON	PLASTIC ROTOFLAME RF1001
	PLASTIC ROTOTHENE R2010
	PLASTIC ROTOTHENE R8107U
	PLASTIC ROTOTHENE R8307U
	PLASTIC ROTOTHENE R835U
	PLASTIC ROTOTHENE R8405
	PLASTIC ROTOTHON XP1
ROTRONIC	LAMIN PC BOARD #H3C WMCKT BRD DEVELOPMENT
ROTRONIC INSTRUMENT CORP	WIRE CABLE SHIELDED
ROYAL INDUSTRIES	LUBE ROYCO 13D
	SEALANT GRAPHITE FILLED TEFLON
	TEFLON TFE/15% GRAPHITE
ROYAL LUBRICANTS	COMPOUND ANTI-SEIZE ROYCO 44
ROYAL SEALS	RUBBER BUTYL R/S 201-6
	RUBBER FLUOROCARBON 102-7
RTE CORP	ADHESIVE EPIC 0104
	ADHESIVE EPIC 701
	ADHESIVE EPIC R1011
	ADHESIVE EPIC R103D
	ADHESIVE EPIC R2027
	ADHESIVE EPIC R3500
	ADHESIVE EPIC S7002
	ADHESIVE EPOC RESIN 0108
	ADHESIVE R1003
	ADHESIVE R1007
	ADHESIVE R3500
	PLASTIC 14B
	PLASTIC 21B 100% REGRIND
	PLASTIC EPIC RESINS P6001
	PLASTIC EPIC RESINS P6004
	PLASTIC PWB 14A

MSFC-HDBK-527 REV F 9999942 0006949 6

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
RTE CORP	PLASTIC PWB 14A 100% REGIND
	PLASTIC PWB 14A VIRGIN
	PLASTIC PWB 14A VIRGIN WITH 20% REGRIND
	PLASTIC PWB 14A VIRGIN WITH 50% REGRIND
	PLASTIC PWB 14B 100% REGRIND
	PLASTIC PWB 14B VIRGIN
	PLASTIC PWB 14B VIRGIN WITH 20% REGRIND
	PLASTIC PWB 14B VIRGIN WITH 50% REGRIND
	PLASTIC PWB 21A
	PLASTIC PWB 21A 100% REGRIND
	PLASTIC PWB 21A VIRGIN
	PLASTIC PWB 21A VIRGIN WITH 20% REGRIND
	PLASTIC PWB 21A VIRGIN WITH 50% REGRIND
	PLASTIC PWB 21B
	PLASTIC PWB 21B VIRGIN
	PLASTIC PWB 21B VIRGIN WITH 20% REGRIND
	PLASTIC PWB 21B VIRGIN WITH 50% REGRIND
	PLASTIC RTP 1000FRA
	PLASTIC RTP 1002FRA
	PLASTIC RTP 1005FR
	PLASTIC RTP 1005FRA
	PLASTIC RTP 101FR
	PLASTIC RTP 103
	PLASTIC RTP 103CC
	PLASTIC RTP 103SP
	PLASTIC RTP 105CC FR
	PLASTIC RTP 1103
	PLASTIC RTP 1105FR
	PLASTIC RTP 1205
	PLASTIC RTP 128
	PLASTIC RTP 1303
	PLASTIC RTP 1378
	PLASTIC RTP 1383
	PLASTIC RTP 1383 TFE 15
	PLASTIC RTP 1385
	PLASTIC RTP 1385 TFE 15
	PLASTIC RTP 1385HEC
	PLASTIC RTP 1387
	PLASTIC RTP 1387HEC
	PLASTIC RTP 1403
	PLASTIC RTP 1405
	PLASTIC RTP 141
	PLASTIC RTP 150
	PLASTIC RTP 152
	PLASTIC RTP 199 X 22898
	PLASTIC RTP 199 X 23835
	PLASTIC RTP 199 X 28016
	PLASTIC RTP 199 X 28016 HI1
	PLASTIC RTP 199 X 28016 HI2
	PLASTIC RTP 199 X 28017C
	PLASTIC RTP 199 X 28559
	PLASTIC RTP 199 X 50148C
	PLASTIC RTP 199 X 50466A
	PLASTIC RTP 199 X 50466B
	PLASTIC RTP 199 X 50485
RTE CORP	PLASTIC RTP 199 X 50486A
	PLASTIC RTP 199 X 50486B
	PLASTIC RTP 199 X 50487B
	PLASTIC RTP 199 X 50487B HI1
	PLASTIC RTP 199 X 50487B HI2
	PLASTIC RTP 199 X 50504
	PLASTIC RTP 199 X 50505
	PLASTIC RTP 199-38016
	PLASTIC RTP 200 TFE 20
	PLASTIC RTP 200FR
	PLASTIC RTP 200MS
	PLASTIC RTP 202FR
	PLASTIC RTP 203
	PLASTIC RTP 203 TFE 20
	PLASTIC RTP 203A
	PLASTIC RTP 203D
	PLASTIC RTP 203H
	PLASTIC RTP 204FR
	PLASTIC RTP 205D FR
	PLASTIC RTP 205FR
	PLASTIC RTP 205MS
	PLASTIC RTP 2105
	PLASTIC RTP 2205
	PLASTIC RTP 225
	PLASTIC RTP 283
	PLASTIC RTP 283 TFE 10
	PLASTIC RTP 285
	PLASTIC RTP 285 TFE 15
	PLASTIC RTP 285HEC
	PLASTIC RTP 285P
	PLASTIC RTP 287
	PLASTIC RTP 287HEC
	PLASTIC RTP 287P
	PLASTIC RTP 299A 27567
	PLASTIC RTP 301FR
	PLASTIC RTP 303
	PLASTIC RTP 303 TFE 10
	PLASTIC RTP 303FR
	PLASTIC RTP 305 TFE 15
	PLASTIC RTP 305FR
	PLASTIC RTP 307FR
	PLASTIC RTP 383
	PLASTIC RTP 383 TFE 20
	PLASTIC RTP 383FR
	PLASTIC RTP 385
	PLASTIC RTP 385 TFE 15
	PLASTIC RTP 385HEC
	PLASTIC RTP 387
	PLASTIC RTP 387HEC
	PLASTIC RTP 403
	PLASTIC RTP 503
	PLASTIC RTP 603
	PLASTIC RTP 685
	PLASTIC RTP 685HEC
	PLASTIC RTP 687

MSFC-HDBK-527 REV F 9999942 0006950 2

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
RTE CORP	PLASTIC RTP 687HEC
	PLASTIC RTP 703
	PLASTIC RTP 783
	PLASTIC RTP 799 X 50492
	PLASTIC RTP 800 TFE 20
	PLASTIC RTP 803
	PLASTIC RTP 805 TFE 15
	PLASTIC RTP 885
	PLASTIC RTP 903
	PLASTIC RTP 905
	RUBBER RTP 1203-80D
	RUBBER RTP 1203-90A
	RUBBER RTP 1299 X 34515B
	RUBBER RTP 1503-40D
	RUBBER RTP 1503-55D
RTS SYSTEMS	MICROPHONE PREAMP 1400
RUBATEX	RUBBER SILICONE NOC
	SPONGE RUBBER NEOPRENE R422N
	SPONGE RUBBER NEOPRENE R425N
RUBBER CTD FABRICS	FABRIC RCF 328-1C
RUBBER SPECIALTIES	SEALANT SILICONE/FEP TEFLON
RUBBERCRAFT	RUBBER NEOPRENE
	RUBBER SILICONE EXTREME LOW TEMPERATURE
	LOW TEMPERATURE HARDNESS SHORE "A" 65-75
	RUBBER SILICONE HARDNESS SHORE "A" 55-65
	RUBBER SILICONE RUBBERCRAFT 59
	RUBBER SYNTHETIC MS35489
RUBBERMAID	SPATULA RUBBERMAID 1904
RUCO POLYMER	FILM RUCOTHANE CO-A769 POLYURETHANE
	INK BLADDER MARKING URETHANE
RUSTOLEUM	COATING EPOXY WHITE 9392/10A00528
	COATING RUSTOLEUM
	COATING RUSTOLEUM X60
	PRIMER ZINC-SELE 9334 GREEN
RYAN INSTRUMENTS	PLASTIC LEXAN 2014 POLYCARBONATE
S/N ID221290	COMPOSITE VITON E60C/NOMEX HT426
SAFETECH	KNEEBOARD ASSEMBLY WITH MECHANICAL PENCIL
SAN FRANCISCO	FILM CR39
SANDSTROM PRODUCTS	LUBE DRY DRILUBE 6A
	LUBE SANDSTROM 9A
SANFORD CORP	INK MARKER PEN 2500/JCP E20
	INK MARKER PEN 2500/PAPER
	INK SHARPIE 3000
	INK SHARPIE PEN 59
	INK TEC BLACK
	INK TEC BLACK #1501
	PEN EXPRESSO 2901/2902N RED
	PEN SHARPIE 3000 BLK
	PEN SHARPIE 35001
SANGRAY CORP	FABULON
SANTA FE TEXTILES	CERAMIC BRAID SLEEVING SF2600
	CORD SF429 GLASS/TFE COATED
	ROPE FIBERGLASS/TFE COATED SF200
	TUBING FIBERGLASS "S"
	TUBING KEVLAR 49
SANTA FE TEXTILES	YARN GLASS/TFE SF-542
SANYO	BATTERY CR2430 3V LITHIUM
	BATTERY LITHIUM LF 1/2W
SARGENT INDUSTRIES	RUBBER NITRILE
	RUBBER SILICONE NOC
	RUBBER SILICONE TH1217
	RUBBER SR2702-75
	RUBBER VITON FLUID RESISTANT
	RUBBER VITON SR2702-72
	SEALANT FLUOROCARBON M83248/2-916
	SEALANT FLUOROCARBON MS83248/2-904
SARSTEDT	MICROHEMATOCRIT TUBE HOLDER
SAUEREISEN CEMENT CO	ADHESIVE SAUEREISEN #29 INORGANIC
	ADHESIVE SAUEREISEN #8 INORGANIC
	CEMENT #78 (INORG)
SAUNDERS ENGINEERING	TAPE THERMOSEAL TFE TEFLON S12
	TEFLON PFA S160 #10299
SCHAAL ASSOCIATES	TUBING TEFLON TFE HST
SCHENECTADY CHEMICAL	INSULATION ENAMEL #300 RED
SCHENECTADY VARNISH	COATING ISONEL 31 POLYESTER
SCHERER LABORATORIES	PAPER GRAPHICS CONTROL ELECTROSTATIC COPY
	P/N 4036R WITH VERSATEC TYPE H/V80 TONER
	TOOTHPASTE NASADENT IN TUBE
SCHRADER	LAQUER YELLOW
SCHULTZ CO	MULTI-LAYERED INSULATION AL/FEP/DACRON/ POLYMIDE
	MULTI-LAYERED INSULATION AL/MYLAR/KEVLAR/ DACRON
SCIENTIFIC ENTERPRISES	FILM ACLAR 933A
	INSULATION FOAM WIPES MICRO-CLEAN POLYURETHANE
SCIENTIFIC INC	GLOVE PVC DISPOSABLE
SCOTFOAM CORPORATION	INSULATION FOAM PYROCUSHION HF300-18
	INSULATION FOAM PYROCUSHION HF325-48
	INSULATION FOAM PYROTHANE LS
SCOTT AVIATION	ADHESIVE SCOTT 101
	FABRIC NETTING/POLYPROPYLENE
	INSULATION FOAM POLYESTER OPEN CELL
	RUBBER 10006149
	RUBBER EPDM 12045-01
	RUBBER EPR ER-WR-EPDM
	RUBBER EPR NCLS1
	RUBBER NEOPRENE
	RUBBER NEOPRENE NCR
	RUBBER NEOTEX ELASTIC
	RUBBER NITRILE NCLS1
	SHIELD POLYCARBONATE PLASTIC
SCOTT PAPER CO	CARDS CUE PAPER
	INSULATION FOAM POLYETHER C190-39 GREEN
	INSULATION FOAM POLYETHER/POLYURETHANE OPEN CELL
	INSULATION FOAM POLYURETHANE HYFONIC 1
	INSULATION FOAM PYRELL
	INSULATION FOAM PYRELL ACOUSTICAL
	INSULATION FOAM PYRELL INSIDE BOX

MSFC-HDBK-527 REV F 9999942 0006951 4

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
SCOTT PAPER CO	INSULATION FOAM PYRELL PC210 COATING
	INSULATION FOAM PYRELL UNCOATED
	INSULATION FOAM PYRELL UNCOATED AND COATED RL4389
	INSULATION FOAM PYRELL WITH REFSET COATING
	INSULATION FOAM PYRELL/DC3140/UBS-N136
	INSULATION FOAM PYRELL/FC273 COATING
	INSULATION FOAM PYRELL/PLV2000 HS COATED
	INSULATION FOAM PYRELL/REFSET RL4389 COATED
	INSULATION FOAM PYRELL/RTV 3140 COATING
	INSULATION FOAM PYROTHANE GRADE 40/25
	INSULATION FOAM PYROTHANE GRADE 45/35
	INSULATION FOAM PYROTHANE GRADE 45/45
	INSULATION FOAM SCOTT CUSTOM GRADE 80 PPI
	INSULATION FOAM SCOTT FILTER PPI XX
	INSULATION FOAM SCOTT INDUSTRIAL
	INSULATION FOAM SCOTT S150-50 GRAY
	INSULATION FOAM SCOTTFELT 10-900 FR POLYURETHANE
	INSULATION FOAM SCOTTFELT 3-900 FR POLYURETHANE
	INSULATION FOAM SCOTTFELT GRADE 700ZH
	INSULATION FOAM SCOTTFELT INSULATION
	INSULATION FOAM URETHANE/ARMALON/CSR300 ADHESIVE
	INSULATION FOAM URETHANE/BLACK VINYL COVER PAPER SCOTT #60
SCOTTFELD	INSULATION FOAM OMALON 1 FR/ACOUSTFAB LINER
	INSULATION FOAM OMALON 1 POLYURETHANE FR
SCOVILL	BRAID ELASTIC POLYESTER
	BRAID ELASTIC POLYESTER/RUBBER
	TAPE ELASTIC RUBBER
	ZIPPER 32" 5283-021B-4A40-0030
	ZIPPER ASSEMBLY NOMEX
	ZIPPER BRASS/NYLON/MYLAR
	ZIPPER NOMEX/BRASS
	ZIPPER TFE/FIBERGLASS/NOMEX
SCUBAPRO INC	RUBBER NEOPRENE MOUTHPIECE
SEA WIRE AND CABLE	CABLE ELECTRICAL SEA BL125
SEAL DYNAMICS	RUBBER VITON A V23
SEARS ROEBUCK & CO	COATING EPOXY ENAMEL 66208 WHITE
	COATING QUICK 65918
SEASTROM	MELAMINE WASHERS
SEBRO THREAD CORP	THREAD NYLON (ALL TYPES)
	THREAD NYLON STRETCH 7
SEE TEST NO.18392	HOSE R502-8 TEFLON
SEE TEST NO.18471	MULTI-LAYERED INSULATION KAPTON/NOMEX/AU/TG 15000
SEE TEST NO.84-18204	GRAPHITE FIBERITE HMF EPOXY
SEE TEST NO.84-18205	COATING EPOXY 463-12-8/A276
SEE TEST NO.85-18390	HOSE R502-16Z TEFLON
SEE TEST NO.85-18394	HOSE R502-6 TEFLON
SEE TEST REPORT	INSULATION TG15000/TI/TAPE 853/KAP
SEE TEST REPORT	MULTI-LAYERED INSULATION KAPTON/DACRON/BETA COVERED
	RUBBER SILICONE HT 2-80 SHOCK ISOLATOR
	WIRE ELEC RAYCHEM 44 ALL GAGES
SEE TEST REPORT/HAZ TEST	BATTERY THIONYL CHLORIDE
SENNHEISER ELECTRONICS	EARPHONE HD-424
SENTRY/EASTERN CHEMICAL LAC	COATING YELLOW 33798 PRIMER/EPOXY TOPCOAT
SEOLOC SCREENING INC	TAPE 003004SX1014 COLOR 4 ANODIZED ALUMINUM WITH PS ACRYLIC ADHESIVE
	TAPE ANODIZED ALUMINUM/ACRYLIC PRESSURE SENSITIVE
SERRA MANUFACTURING	TEFLON TFE VIRGIN
SHAMROCK CORP	TAPE LATEX ST10
SHANNON LUMINOUS	RELEASE AGENT MS143/DYEPEN
SHARP	PAPER E-20 WITH PPC TONER SF-88T
SHELDAHL	ADHESIVE DENSIL 2078 SILICONE
	ADHESIVE DENSIL/KAPTON
	ADHESIVE EPOXY T1401
	ADHESIVE SHELDAHL AKC012
	ADHESIVE SHELDAHL L1662
	ADHESIVE SHELDAHL MKC021
	ADHESIVE SHELDAHL T100
	ADHESIVE SHELDAHL T1502
	ADHESIVE SHELDAHL T1633
	ADHESIVE SHELDAHL T1650
	ADHESIVE SHELDAHL T1694
	ADHESIVE SHELDAHL T300
	ADHESIVE SHELDAHL T329
	ADHESIVE SHELDAHL T340
	ADHESIVE SHELDAHL T400
	COATING CONDUCTIVE INK #703-5-1
	FILM G099700 VAC DEPOSITED ALUMINUM .5 MIL KAPTON STYLE 108 GLASS FABRIC WITH 3P ADHESIVE
	FILM G127200 VAC DEPOSITED ALUMINUM .5 KAPTON STYLE 112 GLASS FABRIC WITH 3P ADHESIVE
	FILM G145100 .5 MIL KAPTON .9 OZ PER SQUARE YARD NOMEX SCRIM
	FILM G402474 VAL/POLYIMIDE
	FILM G412020 KAPTON/ALUMINUM/ORGANIC COATED
	FILM G412500 POLYIMIDE/ARAMID
	FILM G413200 FEP/POLYIMIDE
	FILM G414000 POLYIMIDE/GLASS
	FILM KAPTON ALUMINIZED
	FILM KAPTON GOLDIZED
	FILM KAPTON POLYIMIDE
	FILM POLYIMIDE/ALUMINUM/NOMEX/SCRIM
	FILM TEFLON SILVER COATED
	INSULATION BLANKET FLUORGLAS 385-3
	INSULATION FOAM PDL4034 COVERED WITH L-T-80 TAPE AND THEN G401000 TAPE

MSFC-HDBK-527 REV F 9999942 0006952 6

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
SHELDAHL	INSULATION GLASS FAB/AL FOIL 104
	INSULATION LAMINATE MARQUISETTE
	INSULATION TG15000/MYLAR/FEP TAPE
	LINER FEP/KEVLAR/KAPTON/POLYES
	MULTI-LAYERED INSULATION AL/FEP/DACRON/ POLYMIDE
	MULTI-LAYERED INSULATION AL/MYLAR/KEVLAR/ DACRON
	MULTI-LAYERED INSULATION FEP/GLASS/ POLYIMIDE/KEVLAR
	MULTI-LAYERED INSULATION HITCO TG15000/ G134600 GOLDIZED KAPTON
	MULTI-LAYERED INSULATION RADIATION SHIELD
	MULTI-LAYERED INSULATION RADIATION SHIELD TEFLON
	SHIELD RADIATION
	STRAP ELEC AL KAPTON/PBI
	TAPE AL/KAPTON/ORGANIC COATED
	TAPE G103760 FEP/ARAMID
	TAPE G143902 TFE/GLASS/GOLD/SILICONE ADHESIVE
	TAPE G148000 VACUUM DEPOSITED ALUMINUM X 0.5 MIL KAPTON X 3P ADHESIVE X 0.9 OUNCE
	TAPE G148020 AL/POLY/NOMEX/ADHESIVE
	TAPE G400200 2.0 MIL TYPE A TEFLON WITH VAC DEPOSITED ALUMINUM WITH 966 ACRYLIC ADHESIVE
	TAPE G400300 2 MIL TYPE A TEFLON WITH VACUUM DEPOSITED SILVER AND INCONEL
	TAPE G400600 .5 MIL TYPE A TEFLON WITH VAC DEPOSIT SILVER WITH VAC DEPOSITED INCONEL WITH 966 ACRYLIC ADHESIVE
	TAPE G401000 VACUUM DEPOSITED ALUMINUM 1 MIL KAPTON WITH 966 ACRYLIC ADHESIVE
	TAPE G401900 5 MIL TYPE A TEFLON WITH VAC DEPOSITED SILVER AND INCONEL WITH 966 ACRYLIC ADHESIVE
	TAPE G401902 FEP WITH 467 ACRYLIC ADHESIVE
	TAPE G402410 VACUUM DEPOSITED ALUMINUM 1 MIL KAPTON
	TAPE G402600 VACUUM DEPOSITED GOLD 1 MIL KAPTON WITH MYSTIC 7361 SILICONE ADHESIVE
	TAPE G404200/G404202TFE/AG/SILICONE ADHESIVE
	TAPE G404300/G404302 5 MIL TYPE A TEFLON WITH VACUUM DEPOSITED SILVER AND INCONEL WITH PERMACEL 223 SILICONE ADHESIVE
	TAPE G405110 1 MIL KAPTON WITH VACUUM DEPOSITED ALUMINUM
	TAPE G406400/G406402 VACUUM DEPOSITED GOLD AND 1 MIL KAPTON WITH ACRYLIC ADHESIVE
	TAPE G406510 1 MIL TEFLON WITH 966 ACRYLIC ADHESIVE
	TAPE G406520 2 MIL TEFLON WITH 966 ACRYLIC ADHESIVE
SHELDAHL	TAPE G406550 5 MIL TEFLON WITH 966 ACRYLIC ADHESIVE
	TAPE G40700 KAPTON/GOLD ADHESIVE
	TAPE G407700 KAPTON VACUUM DEPOSITED ALUMINUM WITH SILICONE ADHESIVE
	TAPE G407810 VACUUM DEPOSITED ALUMINUM 1 MIL KAPTON WITH 1 MIL SILICONE ADHESIVE
	TAPE G407910 VACUUM DEPOSITED GOLD 1 MIL KAPTON WITH SILICONE ADHESIVE
	TAPE G407925 PS ADHESIVE
	TAPE G408100 INCONEL SILICONE ADHESIVE
	TAPE G408150 5 MIL TEFLON VACUUM DEPOSITED SILVER AND INCONEL WITH 1 MIL SILICONE AD HESIVE
	TAPE G408460 THICK BLACK FILM WITH .5 MIL KAPTON AND 1 MIL SILICONE ADHESIVE
	TAPE G408862 ALUMINUM/KAPTON/ADHESIVE
	TAPE G409360 THICK BLACK FILM WITH .5 MIL KAPTON AND 966 ACRYLIC ADHESIVE
	TAPE G411520 2 MIL§RÎ KAPTON VACUUM DEPOSITED ALUMINUM WITH ACRYLIC OVERCOAT
	TAPE G411600 AL-KAPTON/ORGANIC COATED
	TAPE G411660 5 MIL KAPTON WITH VACUUM DEPOSITED ALUMINUM
	TAPE G411970 ALUMINUM/KAPTON/ADHESIVE
	TAPE G412400 FEP/POLYIMIDE/ARAMID
	TAPE POLYIMIDE AU/AL PS ADHESIVE
	TAPE REINFORCED 536-34-2 GOLD
	TAPE TEFLON FEP
	TAPE TEFLON FEP 4043 AG INCONEL WITH T223 ADHESIVE
	TAPE THERMOSET
	WIRE ELEC TEFLON TFE
SHELL CHEMICAL	ADHESIVE 18540 11C/EPON H2 CURE
	ADHESIVE 828/872/PAPA/EMI-24
	ADHESIVE EA828/VERSAMID 140 1/1BW
	ADHESIVE EPON 1001F
	ADHESIVE EPON 1001F/VERSAMID 115
	ADHESIVE EPON 1002F
	ADHESIVE EPON 1004F
	ADHESIVE EPON 1007F
	ADHESIVE EPON 1009F
	ADHESIVE EPON 1031
	ADHESIVE EPON 1031A-70
	ADHESIVE EPON 1031B-80
	ADHESIVE EPON 812
	ADHESIVE EPON 813
	ADHESIVE EPON 8132
	ADHESIVE EPON 815 EPOXY
	ADHESIVE EPON 815 WITH EPOCAST HN951
	ADHESIVE EPON 815/CAT Z EPOXY
	ADHESIVE EPON 815/DTA
	ADHESIVE EPON 815/DTA/PHENOLIC F
	ADHESIVE EPON 815/EPC190/AP5
	ADHESIVE EPON 815/EPC190/AP5V

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006953 8

MANUFACTURER	DESIGNATION
SHELL CHEMICAL	ADHESIVE EPON 815/MDA EPOXY
	ADHESIVE EPON 815/RF61/GL FT102
	ADHESIVE EPON 815/V15
	ADHESIVE EPON 815/V25
	ADHESIVE EPON 820/CAT U EPOXY
	ADHESIVE EPON 8201/CAT Z/HMS FIBE
	ADHESIVE EPON 823
	ADHESIVE EPON 825
	ADHESIVE EPON 825/EPICURE 855
	ADHESIVE EPON 825/HV
	ADHESIVE EPON 825/HV/MEK-V
	ADHESIVE EPON 826/1031/EMI24
	ADHESIVE EPON 826/1031/NMA/EMI24
	ADHESIVE EPON 826/1031/NMA/PYRADINE
	ADHESIVE EPON 826/BDE/T6040
	ADHESIVE EPON 826/BF3MEA
	ADHESIVE EPON 826/DADS/BF3MEA
	ADHESIVE EPON 826/DDS/BF3MEA
	ADHESIVE EPON 826/HHPA/BDMA
	ADHESIVE EPON 826/MPDA
	ADHESIVE EPON 826/MPDA/ANILINE
	ADHESIVE EPON 826/MTHPA/BDMA
	ADHESIVE EPON 826/NMA/EMI24
	ADHESIVE EPON 826/PAPA/BDMA
	ADHESIVE EPON 826/Y
	ADHESIVE EPON 826/Z
	ADHESIVE EPON 828 EPOXY
	ADHESIVE EPON 828/1031/EMI24
	ADHESIVE EPON 828/1031/MTHPA/EMI24
	ADHESIVE EPON 828/1031/Y
	ADHESIVE EPON 828/871/AEP
	ADHESIVE EPON 828/871/MDA
	ADHESIVE EPON 828/871/NMA/EMI24
	ADHESIVE EPON 828/871/Z
	ADHESIVE EPON 828/872/AEP
	ADHESIVE EPON 828/872/Z
	ADHESIVE EPON 828/AEP
	ADHESIVE EPON 828/BF3MEA
	ADHESIVE EPON 828/C906
	ADHESIVE EPON 828/CA
	ADHESIVE EPON 828/CAT U EPOXY
	ADHESIVE EPON 828/D
	ADHESIVE EPON 828/D230
	ADHESIVE EPON 828/D230/AEP
	ADHESIVE EPON 828/D400
	ADHESIVE EPON 828/DADS
	ADHESIVE EPON 828/DADS/BF3MEA
	ADHESIVE EPON 828/DDSA/EMI24
	ADHESIVE EPON 828/DETA
	ADHESIVE EPON 828/DSA/BDMA
	ADHESIVE EPON 828/DTA 7500 GLASS
	ADHESIVE EPON 828/DTA EPOXY
	ADHESIVE EPON 828/DTA EPOXY GL FL
	ADHESIVE EPON 828/EM308 EPOXY
	ADHESIVE EPON 828/EMI24

MANUFACTURER	DESIGNATION
SHELL CHEMICAL	ADHESIVE EPON 828/EMPOL1040/DMP10
	ADHESIVE EPON 828/EPOCAST HN951
	ADHESIVE EPON 828/HHPA/BDMA
	ADHESIVE EPON 828/HHPA/DMP30
	ADHESIVE EPON 828/HHPA/EMI24
	ADHESIVE EPON 828/IPD
	ADHESIVE EPON 828/L ARAMINE C260
	ADHESIVE EPON 828/LP3/DMP30
	ADHESIVE EPON 828/MDA
	ADHESIVE EPON 828/MDA/DMP30
	ADHESIVE EPON 828/MPDA
	ADHESIVE EPON 828/MPDA/SILICA FILLER
	ADHESIVE EPON 828/MTHPA/BDMA
	ADHESIVE EPON 828/NMA/BDMA
	ADHESIVE EPON 828/PA/BDMA
	ADHESIVE EPON 828/PACM20
	ADHESIVE EPON 828/PAPA/BDMA
	ADHESIVE EPON 828/PAPA/EMI24
	ADHESIVE EPON 828/PMDA
	ADHESIVE EPON 828/RP7A EPOXY
	ADHESIVE EPON 828/T1
	ADHESIVE EPON 828/TETA
	ADHESIVE EPON 828/THPA/BDMA
	ADHESIVE EPON 828/THPA/EMI24
	ADHESIVE EPON 828/V40
	ADHESIVE EPON 828/VERSAMID 120
	ADHESIVE EPON 828/VERSAMID 125
	ADHESIVE EPON 828/VERSAMID 140
	ADHESIVE EPON 828/Y
	ADHESIVE EPON 828/Z CURING AGENT
	ADHESIVE EPON 828/ZZLA0822
	ADHESIVE EPON 8280
	ADHESIVE EPON 829
	ADHESIVE EPON 8294
	ADHESIVE EPON 830
	ADHESIVE EPON 834
	ADHESIVE EPON 834/NMA/DMP30
	ADHESIVE EPON 834/THPA/DMP30
	ADHESIVE EPON 836
	ADHESIVE EPON 841
	ADHESIVE EPON 871
	ADHESIVE EPON 871/PAPA/EMI24
	ADHESIVE EPON 872
	ADHESIVE EPON 872/828/HHPA/DMP30
	ADHESIVE EPON 872/828/V40
	ADHESIVE EPON 872/871/AEP
	ADHESIVE EPON 872/871/AEP/OCTYL AMINE
	ADHESIVE EPON 872X75
	ADHESIVE EPON DPS164
	ADHESIVE EPON/871/DDSA/EMI24
	ADHESIVE EPON/NMA/EMI-24
	ADHESIVE POLYAMIDE V40
	COATING EPICEL 3 EPOXY/CURE AGENT U
	COATING EPON 1001/VERSAMID 115

MSFC-HDBK-527 REV F 9999942 0006954 T

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
SHELL CHEMICAL	COATING EPOXY WHITE TOPCOAT WITH H2 CATALYST
	COATING WHITE EPOXY/H2
	GREASE AEROSHELL 17
	INSULATION FOAM SYNTACTIC EPON 815
	INSULATION FOAM SYNTACTIC EPON 815/KEVLAR
	LAMIN EPOXY/GLASS EPON APCO 434/SONITE 41
	LAMIN/EPOXY/GLASS EPON 815/GLASS 7781/DTA
	LAMIN/EPOXY/GLASS/EPON 815/GLASS 112/DTA
	LUBE GREASE AEROSHELL XSG6249
	POTTING COMPOUND EPON 828/ALUMINUM/TONOX
	SEALANT PLENUM SHELL CVR POLYURETHANE
	SHELL 405 CATALYST
SHELL CHEMICAL/COAST PRO SEAL	ABLEFILM 561 EPOXY ON GLASS 8/VERSAMID 115
SHELLER GLOBE	CORK P50/ADHESIVE RTV 560
	INSULATION CORK COMPOSITE P50
SHERWIN INC	DEVELOPER D90
	PENETRANT I-319
SHERWIN WILLIAMS	COATING ACRYLIC ENAMEL BLACK
	COATING ACRYLIC ENAMEL SW CLEAR
	COATING ACRYLIC ENAMEL SW J5-5226
	COATING E42GP22/V66KP46 EPOXY
	COATING NA7509-V73/NA7486-V66 PLU
	COATING POLANE ENAMEL
	COATING POLANE F63 VI
	COATING POLANE F63CB2/V66V29
	COATING POLANE TOPCOAT/KEVLAR
	COATING POLYAMIDE EPOXY PRIMER YELLOW
	COATING POLYIMIDE EPOXY YELLOW TC
	COATING POLYURETHANE (ESTER)
	COATING POLYURETHANE CLEAR GLOSS VARNISH ON INSTA-FOAM A67 V1
	COATING TOPCOAT YELLOW
SHIN-ETSU CHEMICAL	POTTING COMPOUND KE45 SILICONE
	RUBBER SILICONE KE941U
	SEALANT SILICONE KE348
	SEALANT SILICONE KE44
	SPONGE RUBBER SILICONE KE901FU
SHORE-UBS CHEM CO	ADHESIVE N136
SHOWA ELECTRIC WIRE & COMPANY	WIRE P1W C-7 POLYIMIDE
SHUFORD MILLS	TAPE SHURTAPE PC28F B/L B1255
SHULTON INC	DEODORANT OLD SPICE SOLID
SIB DIELECTRIC COMM	ABSORBER RF IRON/EPOXY EMA 719
SIERRA ENGINEERING	ALTITUDE OXYGEN HOSE
	RUBBER SILICONE SWS7220
	VALVE NON-REBREATHER
SIERRACIN/HARRISON	COATING 851-255 BLACK/850-204 TFE
	COATING PRIMER/ENAMEL TFE
	FABRIC GLASS/SILICONE
	K-6 ALLOY TEST DISCS
SIKA CHEMICAL	ADHESIVE SIKA 15LM
	ADHESIVE SIKAFLEX 1A
	ADHESIVE SIKAFLEX 2C NS/NL
SIKKENS	COATING 643-18-1 WHITE
	COATING EPOXY PRIMER 37051
	COATING TEMP CONTROL POLYURETHANE/AL
SIMMONDS	PASTE 97% GOLD ELECTRICAL COND
SIMPLOT	HERBICIDE BOROSIL 4 SEE REPORT
SINCLAIR	COATING LAC-O-RITE
SINCLAIR & RUSH	TUBING POLYOLEFIN GPF135 HST
SINGER KEARFOTT	LAMIN GT100/GT420/GT10/QR43117
	LAMIN OVERCOAT WITH 1B31/FC721
	WIRE ELEC ETFE TEFZEL
SIRLSA PRODUCTS	DISH SOAP HSB 2
SKILCRAFT	PEN FELT TIP BEIGE
	PEN FELT TIP PURPLE
	PENCIL SKILCRAFT MECHANICAL
SKINNER VALVE	ADHESIVE EPOXY V5H734R24
SMALLCOMB ELECTRIC	DUCTING RUBBER IMPREG COTTON
SMITH	TAPE ELASTIC .75 WIDE
SMITH ALSOP	CORK P50/COATING 051-A69
SMOOTH-ON INC	ADHESIVE METALSET A4 EPOXY
	LAMIN EPOXY/GLASS EPON APCO 434/SONITE 41
SNAP-ON-TOOLS	DRIVER IMPACT PIT-120
	HAMMER BALLPEEN P/N BP-N-4A
	HANDLE DRIVER F40A
	HANDLE DRIVER F50
SOLAR TURBINES	INSULATION FOAM POLYIMIDE 1702
	INSULATION FOAM POLYIMIDE 1720
SOLEX	PLASTIC FORTIFLEX T504400119
SOLOPAK	FILM MYLAR POLYLOK
	PAPER COATED
SOLTEX	PLASTIC FORTIFLEX A6070119
	PLASTIC FORTIFLEX B3514F
	PLASTIC FORTIFLEX B35150134
	PLASTIC FORTIFLEX B4506R09
	PLASTIC FORTIFLEX B5020H
	PLASTIC FORTIFLEX B5035H
	PLASTIC FORTIFLEX B5335H
	PLASTIC FORTIFLEX B5335H100
	PLASTIC FORTIFLEX B5335H126
	PLASTIC FORTIFLEX B5425H
	PLASTIC FORTIFLEX B5425H124
	PLASTIC FORTIFLEX B5425H127
	PLASTIC FORTIFLEX F444A
	PLASTIC FORTIFLEX F469A
	PLASTIC FORTIFLEX F622
	PLASTIC FORTIFLEX G6025119
	PLASTIC FORTIFLEX G6080F
	PLASTIC FORTIFLEX J60100130
	PLASTIC FORTIFLEX K3411121
	PLASTIC FORTIFLEX K3655123
	PLASTIC FORTIFLEX K3820137
	PLASTIC FORTIFLEX K4411128
	PLASTIC FORTIFLEX K4415123
	PLASTIC FORTIFLEX K4424123
	PLASTIC FORTIFLEX K5030135
	PLASTIC FORTIFLEX T353500129

MSFC-HDBK-527 REV F 9999942 0006955 1

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
SOLTEX	PLASTIC FORTIFLEX T35600
	PLASTIC FORTIFLEX T491000129
	PLASTIC FORTIFLEX T501000
	PLASTIC FORTIFLEX T50200
	PLASTIC FORTIFLEX T502000
	PLASTIC FORTIFLEX T503600119
	PLASTIC FORTIFLEX T50500
	PLASTIC FORTIFLEX T505500119
	PLASTIC FORTIFLEX T601500
	PLASTIC FORTIFLEX T603000119
	PLASTIC FORTIFLEX T604200119
	PLASTIC FORTIFLEX T60500
	PLASTIC FORTIFLEX T60800
	PLASTIC FORTIFLEX XF337G
	PLASTIC FORTIFLEX XF397D
	PLASTIC FORTIFLEX XF409
	PLASTIC FORTIFLEX XF448
	PLASTIC FORTIFLEX XF451
	PLASTIC FORTIFLEX XF455
	PLASTIC FORTIFLEX XF470
	PLASTIC FORTIFLEX XF480A
	PLASTIC FORTIFLEX XF528B
	PLASTIC FORTIFLEX XF591H
	PLASTIC FORTIFLEX XF600
	PLASTIC FORTIFLEX XF621
	PLASTIC FORTILENE 10 X 03
	PLASTIC FORTILENE 1001
	PLASTIC FORTILENE 1401
	PLASTIC FORTILENE 1420
	PLASTIC FORTILENE 1602
	PLASTIC FORTILENE 1602A
	PLASTIC FORTILENE 1604
	PLASTIC FORTILENE 1802
	PLASTIC FORTILENE 1803
	PLASTIC FORTILENE 1804
	PLASTIC FORTILENE 1805
	PLASTIC FORTILENE 1902
	PLASTIC FORTILENE 1903
	PLASTIC FORTILENE 21 X 04
	PLASTIC FORTILENE 22 X 02
	PLASTIC FORTILENE 2251
	PLASTIC FORTILENE 3151
	PLASTIC FORTILENE 3251
	PLASTIC FORTILENE 3606
	PLASTIC FORTILENE 3651
	PLASTIC FORTILENE 3807
	PLASTIC FORTILENE 39 X 09
	PLASTIC FORTILENE 3907
	PLASTIC FORTILENE 40 X 05
	PLASTIC FORTILENE 41 X 03
	PLASTIC FORTILENE 41 X 11
	PLASTIC FORTILENE 4104
	PLASTIC FORTILENE 4109
	PLASTIC FORTILENE 4110
	PLASTIC FORTILENE 4141

MANUFACTURER	DESIGNATION
SOLTEX	PLASTIC FORTILENE 4207
	PLASTIC FORTILENE 4208
	PLASTIC FORTILENE 4306
	PLASTIC FORTILENE 45 X 02
	PLASTIC FORTILENE 5402
	PLASTIC FORTILENE 90 X 02
	PLASTIC FORTILENE 9000
	PLASTIC FORTILENE 9005
	PLASTIC FORTILENE 9101
	PLASTIC FORTILENE 9200
	PLASTIC FORTILENE 9205
	PLASTIC FORTILENE 9226
	PLASTIC FORTILENE 9600
	PLASTIC FORTILENE 9605
	PLASTIC FORTILENE 9625
SOLUOL CHEMICAL CO	ADHESIVE SOLUBOND 1119
	ADHESIVE SOLUBOND 1121
	ADHESIVE SOLUBOND 1122
	ADHESIVE SOLUBOND 1168
	ADHESIVE SOLUBOND 1173
	ADHESIVE SOLUBOND 1177
SONFARREL	RUBBER SILICONE SONFARREL 1151
SOUNDCOAT	ABSORBER SOUND GP-2 DAMPING
	FOAM SOUNDFOAM "HT" POLYIMIDE
	FOAM SOUNDFOAM "HT" POLYIMIDE WITH NOMEX FABRIC FACING
	FOAM SOUNDFOAM 'M' POLYURETHANE
SOUNDCRAFT INC	RUBBER DYAD 606
SOUTHERN MILLS	COATING POLYURETHANE TOPCOAT #1
	CONFIG/SEE 20406/20579
	FABRIC NOMEX 3 ARAMD/NO FINISH
	FABRIC NOMEX 3 NO-MO-STAT WITH STAINLESS STEEL NAVY
	FABRIC NOMEX 3 WICKWELL FINISH
	FABRIC NOMEX 3/SCOTCHGARD COATED
	FABRIC NOMEX 3/ZEPEL FINISH
	FABRIC NOMEX 30939 2.5OZ BROWN
	FABRIC NOMEX 30939 2.5OZ ORNG
	FABRIC NOMEX 30939 2.5OZ WHITE
	FABRIC NOMEX 7.5 OZ/ZEPEL
	FABRIC NOMEX DENIM LAUNDERED
	FABRIC NOMEX S/470 LAUNDERED
	FABRIC NOMEX S470/ZEPEL 86900
	FABRIC NOMEX S619
	FABRIC NOMEX S619/ARAMID GRN
	FABRIC NOMEX S619/ZEPEL 69878
	FABRIC NOMEX WITH ZEPEL/ARMALON
	FABRIC NOMEX WITH ZEPEL/ARMALON/URETHANE COATED NY
	FABRIC NOMEX/DENIM BLUE
	FABRIC NOMEX/TEF FILM/NOMEXWEB
	FABRIC NOMEX/ZEPEL COATED
SOUTHERN SILK MILLS	FABRIC FRL 397.356 NOMEX
	FABRIC KEVLAR 29/774
	FABRIC NOMEX C4270

MSFC-HDBK-527 REV F ■ 9999942 0006956 3 ■

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
SOUTHERN SILK MILLS	FABRIC NOMEX SIMPLEX
	FABRIC NOMEX TRICOT STYLE 240
SOUTHLAND CORK	INSULATION CORK AB600
SOUTHWEST KINETICS	INSULATION FOAM URETHANE/POLYETHER N GREY
SOUTHWEST PRODUCT CO	LUBE DRY DYFLON
SOUTHWEST SEAL	RUBBER VITON FLUID RESISTANT
SPACE CITY SHOE REP	SHOE SOLE NEOPRENE 9 IRON
SPAR AEROSPACE	CORD SHOCK RUBBER/KEVLAR/COTTON
	LAMIN FIBERITE 1
SPECIALTY COMPOSITES	INSULATION FOAM CONFOR C40
	INSULATION FOAM CONFOR C45
	INSULATION FOAM CONFOR C47
	INSULATION FOAM TUFCOTE ACOUSTICAL
	INSULATION FOAM TUFCOTE ACOUSTICAL 104
SPECTAPE	TAPE DUCT CLOTH ST260
	TAPE VINYL/COTTON SP252
SPECTRA-STRIP CORP	CABLE ASSEMBLY NYLON/GLASS
SPEIDEL/TEXTRON	DEODORANT BRITISH STERLG SOLID
SPEREX CORP	COATING SILICONE BLACK VHT SP102
	COATING SILICONE WHITE VHT SP101
	LACQUER VHT 1200F SP102 17038
	LACQUER VHT1200F SP101 17875
SPRAGUE	CAPACITOR EMI TVA1966
SPRING MILLS	FABRIC 65 POLYESTER/35 COTTON
ST CLAIR & RUSH	TUBING POLYETHYLENE HST
ST LOUIS BRAID CO	CORD BOOT LACES
ST5M1298-16R2U0	WIRE ELEC 16 AWG CABLE
STABOND CORP	ADHESIVE C111
	ADHESIVE G404
	ADHESIVE N134
	ADHESIVE STABOND C136 NITRILE
	ADHESIVE STABOND N125 NEOPRENE
	ADHESIVE STABOND T161
	ADHESIVE STABOND T190 NEOPRENE
	ADHESIVE T165
	ADHESIVE T440
	ADHESIVE U148
STACY FABRICS	FABRIC COTTON INTERFACING
	FABRIC COTTON SHAPE-FLEX LINING
	FABRIC RAYON GOAT HAIR
STAEDTLER	INK LUMOCOLOR 317
	PEN LUMOCOLOR 313 SF
STANCHEM	INSULATION FOAM ALBI-COTE FRL 5A
	INSULATION FOAM ALBICOTE
	INSULATION FOAM ALBICOTE FRL 3A
	INSULATION FOAM CPR1061 COATED WITH ALBI-COTE FRL WITH COATED SEMICIRCLE
	INSULATION FOAM CPR1061 WITH ALBI COTE COATING
	INSULATION FOAM STICK IU57/ALBICOTE FRL
STANPAT PROD	ADHESIVE STANPAT
STAR GLOVE & SAFETY	GLOVE INSULATED FES 3MF114AP
STATE STAMP INK	INK 977-9
STAUFFER CHEMICAL	ADHESIVE SWS931
	ADHESIVE SWS990

MANUFACTURER	DESIGNATION
STAUFFER CHEMICAL	ADHESIVE SWST60
	LUBE OIL FRIQUIL V220 CELLUBE
	PLASTIC RTV SWS04478
	PLASTIC RTV SWS843
	RUBBER SILICONE SWS7220
STAYLASTIC	CORD NOMEX BRAIDED
STEPAN CHEMICAL	INSULATION FOAM POLYURETHANE ET
STEPAN CHEMICAL CO	INSULATION FOAM BX249N POLYURETHANE
	INSULATION FOAM BX250 VARIOUS RATIO POLYURETHANE
	INSULATION FOAM BX442R(X1057-137A) POLYURETHANE
	INSULATION FOAM BX443R POLYURETHANE
	INSULATION FOAM NOPCO H402-N-T/N-R
	INSULATION FOAM NOPCO G306R/G306T
	INSULATION FOAM RS9412 POLYURETHANE
	INSULATION FOAM STEPAN BX352 URETHANE
	INSULATION FOAM STEPAN BX352M/DC3140 COATED
	INSULATION FOAM STEPAN BX352M/OCEAN CM987
	INSULATION FOAM URETHANE R248E
STEPAN CHEMICAL CO/ RAYBESTOS-MANHATTAN	INSULATION FOAM RS9412 WITH REFSET RL4389 FR COATED
STEPAN CHEMICAL CO/ RAYBESTOS-MANHATTAN/ DOW CORNING	INSULATION FOAM RS9412 POLYURETHANE REFSET RL4389 AND RTV 3140 COATED
STEPAN CHEMICAL/GACO WESTERN	INSULATION FOAM BX250/HYPALON COATED
STEPHENSON & LAWYER	FILM VINYL COTTON TEXLE BACKED
	INSULATION FOAM POLYESTER/PVC FLAME BOND
STERLING DIV OF REICHHOLD CHEMICAL	ADHESIVE U500-25 EPOXY
	COATING 68U-1005/U3380 POLYURETHANE
	COATING ACRYLIC 90-10472 CORROSION PREVENTIVE
	COATING POLYURETHANE CONFORMAL U2863
STERN & STERN	FABRIC AROMATIC/NON-MELTING
	FABRIC CHEMSTAT 919 NOMEX
	FABRIC DACRON 15292
	FABRIC DACRON 15453 7.52 OZ/YD
	FABRIC DPB 65-45 KEVLAR 29
	FABRIC HT-10-41 NOMEX
	FABRIC HT-16-45 NOMEX
	FABRIC HT-195-40 NOMEX
	FABRIC HT-244-36 NOMEX NATURAL
	FABRIC HT-287-45 NOMEX
	FABRIC HT-318-53 NOMEX
	FABRIC HT-318-53 NOMEX NATURAL
	FABRIC HT-46-XX ARAMID WOVEN
	FABRIC HT-472-40 NOMEX/COTTON
	FABRIC HT-473-41 NOMEX/COTTON
	FABRIC HT-5-42 NOMEX
	FABRIC HT-5-42 NOMEX NATURAL
	FABRIC HT-59-62 NOMEX
	FABRIC HT-67-42 NOMEX NATURAL
	FABRIC HT-90-40 NOMEX

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0006957 5

MANUFACTURER	DESIGNATION
STERN & STERN	FABRIC HT-90-40 NOMEX/STN RMVR
	FABRIC HT-96 NOMEX RESIN TREAT
	FABRIC HT-96-62G NOMEX NATURAL
	FABRIC KELVAR 29
	FABRIC NO T-261-36 TEFLON
	FABRIC NOMEX 2PLY
	FABRIC NOMEX 2PLY/FELT-1PLY
	FABRIC NOMEX COATED WITH SCOTCHGARD FC4101
	FABRIC NOMEX HF9254 3.2 OZ
	FABRIC NOMEX HT-49
	FABRIC NOMEX/VELCRO/FC4101
	FABRIC NYLON A2598/15 LT BLUE
	FABRIC NYLON A2634/B 3.8 OZ
	FABRIC NYLON A5691
	FABRIC NYLON CHIFFON
	FABRIC NYLON CHIFFON A5652/4
	FABRIC NYLON MESH NON-MELTING
	FABRIC POLYESTER STYLE 15458
	FABRIC T162-42
	FABRIC TEFLON
	FABRIC TEFLON T-83-54
	FABRIC TEFLON T162
	FABRIC TEFLON T21-42
	FELT NOMEX
	RUBBER VITON E60C/HT426 NOMEX
STEVEN LABEL CORP	INK SCREEN DAYGLO SUPER 67
	INK SUPER 67 ARC YELLOW
	INK SUPER 67 SATURN YELLOW
	INK SUPER 67 SIGNAL GREEN
STEVENS MOLDED PROD	FILM HYTUFF MP2080 POLYURETHANE
	FILM POLYURETHANE HITUFF MP1880
	LAMIN EPOXY/GLASS E720
STILLMAN RUBBER	RUBBER BUTYL
	RUBBER SILICONE TH1006
	RUBBER SILICONE TH1241
	RUBBER SR2702-75
	RUBBER VITON FLUID RESISTANT
STILSON CORP	RUBBER SUCTION CUP
	SUCTION CUP RUBBER STILSON4037
STM 0699-01	COMPOSITE VITON E60C/NOMEX HT426
STOCKWELL RUBBER	RUBBER STOCKWELL 2023
STRATHMORE PAPER CO	PAPER ARTIST 240-5/FASSON 824
	PAPER STRATHMORE SHEETS 100% COTTON FIBER
	SERIES 500 WHITE POSTERBOARD
STREAMLIGHT INC	FLASHLIGHT STREAMLITE 20
STRUCTURAL COMPOSITES	COATING RTV DC Q36077 ABLATIVE/EPON 828/
	EPOCAST 951
	FABRIC KEVLAR 49/EPOXY
	FABRIC KEVLAR EPOXY PANEL
	LAMIN KEVLAR 49/32 EPOXY
	STRAP CARBON GRAPHITE IM-6 EPOXY
	STRAP GLASS S2/EPOXY
STYLASTIC	TAPE ELASTIC .75 WIDE
SUMITOMO	POREFLON P/N FP080 PTFE
	POTTING COMPOUND SUMICERAM S10A
SUMITOMO	TUBING SPECIAL FLEX KYNAR K2
	TUBING SUMITUBE POLYOLEFIN HST
SUN CHEMICAL	FABRIC FACILON 1814 PVC BLUE
	FABRIC FACILON NYLON/VINYL BLU
	FABRIC NYLON/VINYL RED 1024
	INK MARKING WE44 RED
SUPER-TEMP	CARBON/GRAPHITE BONDED
SUPERIOR MRKNG EQUIP	INK TROJAN OPAQUE BLACK
	INK TROJAN OPAQUE SILVER
SUPERIOR VALVE CO	VALVE SUPERIOR 430
SURFKOTE	LUBE FILM SOLID
SWEDLOW	ACRYLIC SHEET SI60948 STRETCH
	ACRYLIC TYPE 350S
SWS SILICONES	ADHESIVE RTV T200
	ADHESIVE RTV T56
	COATING SILICONE BLACK
	COATING SILICONE GLASS/TETRABRN FIL
	FABRIC CERAMIC AB312 SILICONE COATED
	RUBBER SILICONE 934 HEAT SINK
	RUBBER SILICONE RTV SWS930
	RUBBER SILICONE RTV SWS951
	RUBBER SILICONE RTV SWSV81
	RUBBER SILICONE SILIGAN J500
	RUBBER SILICONE SWS7220
	RUBBER SILICONE SWS7220/7250
	RUBBER SILICONE SWS845 CAT KX
SYMETRICS	RUBBER SILICONE 1235-70
SYNAIR	RUBBER DUOTHANE N1545A
	RUBBER DUOTHANE N1545B
	RUBBER DUOTHANE N1545C
	RUBBER DUOTHANE N1545D
	RUBBER DUOTHANE N4209
	RUBBER DUOTHANE N6766
	RUBBER DUOTHANE S300
	RUBBER DUOTHANE S401
	RUBBER DUOTHANE S502
	RUBBER DUOTHANE S504
	RUBBER DUOTHANE S600
	RUBBER DUOTHANE S601
	RUBBER DUOTHANE S602
	RUBBER DUOTHANE S603 (REDCOTE)
	RUBBER DUOTHANE S700
	RUBBER DUOTHANE S701
	RUBBER DUOTHANE S702
	RUBBER DUOTHANE S800
	RUBBER DUOTHANE S802
	RUBBER DUOTHANE S803
	RUBBER DUOTHANE S900
	RUBBER DUOTHANE S901
	RUBBER MONOTHANE A10
	RUBBER MONOTHANE A100
	RUBBER MONOTHANE A20
	RUBBER MONOTHANE A30
	RUBBER MONOTHANE A40
	RUBBER MONOTHANE A40HR

MSFC-HDBK-527 REV F 9999942 0006958 7

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
SYNAIR	RUBBER MONOTHANE A45SR
	RUBBER MONOTHANE A50
	RUBBER MONOTHANE A60
	RUBBER MONOTHANE A70
	RUBBER MONOTHANE A80
	RUBBER MONOTHANE A90
SYNTHANE-TAYLOR CORP	LAMIN COTTON/PHENOLIC
	LAMIN EPOXY/GLASS
	LAMIN EPOXY/GLASS 500
	LAMIN EPOXY/GLASS FB400 GF
	LAMIN EPOXY/GLASS FB600
	LAMIN EPOXY/GLASS FR TYPE GF
	LAMIN EPOXY/GLASS GENERAL PURPOSE
	LAMIN EPOXY/GLASS L-P-509 TYPE G10
	LAMIN EPOXY/GLASS TAYLORCLAD FIREBAN
	LAMIN PHENOLIC/COTTON
	LAMIN PHENOLIC/PAPER
	LAMIN SILICONE/GLASS
	LAMIN SYNTHANE G9 NATURAL
SYNTHETIC TEXTILE	CORD NOMEX 1200 DENIER
	CORD NOMEX 2400 DENIER
SYNTHETIC THREAD	THREAD KEVLAR
	THREAD NOMEX
	THREAD NOMEX SILICONE FINISH
T A MFG CORP	CLAMP CUSHION TA101
	CLAMP SILICONE/FABRIC TA 321
	CLAMP SILICONE/GLASS
	CLAMP SLEEVE TEFLON TFE
	CLAMP ST253/CUSH MOSITES 1059
	CLAMP TA02112 WITH INSUL
	COMPOUND TA2417 SILICONE
	LAMIN FIBERGLASS TA88
	MOLD COMPOUND TA-88-50
	RUBBER SILICONE TA52
	RUBBER SILICONE TA96
	TAPE TA44-2
	TAPE TA88 PS
	TEFLON PTFE DISCS
	TEFLON TFE VIRGIN
T F INDUSTRIES	FABRIC FIBERGLASS 2103/108 TFE
	FABRIC FIBERGLASS/SILICONE 03080
TACONIC PLASTIC LTD	FABRIC BETA CLOTH/TFE GLASS TAPE
	TAPE 6083 TFE/GLASS
TADIRAN	BATTERY THIONYL CHLORIDE
TAKIRON CHEMICAL CO	POLYCARBONATE TAKIRON PANLITE PLATE
TALON	ZIPPER NOMEX/BRASS
	ZIPPER NOMEX/BRASS FIRE/WATER PROOF
	ZIPPER POLYESTER/NYLON COGS
	ZIPPER TALON 705-19 NYLON/BRASS
TANDY LEATHER	LEATHER SUPER SHENE FINISH 2002
TAPECON	FILM COPPER/MYLAR
	TAPE KAPTON/POLYIMIDE 583
TD-RT	KEL-F 800 MEK/SPRAY
TECHNICAL CIRCUITS	LAMIN EPOXY/GLASS GENERAL PURPOSE

MANUFACTURER	DESIGNATION
TECHNICAL COATED FABRICS	NYLON 2257 ALUM-INIZED NEOPRENE COATED WITH 2310 NEOPRENE BIAS TAPE AND N-1030 NEOPRENE ADHESIVE
TECHNICAL FLUOROCARBON	TAPE HI/D 603A KAPTON/ACRYLIC
TECHNICAL SALES	RUBBER VITON O-RING 19357
	RUBBER VITON O-RING CPD 16129
	RUBBER VITON O-RING CPD 16207
	RUBBER VITON O-RING CPD 19447
	RUBBER VITON V709-9
	RUBBER VITON V747-7
	RUBBER VITON V747-75
TECHNICAL WIRE PROD	ADHESIVE SILVER SILICONE
	FELT TECKFELT 45-09811
	RUBBER CONSIL 861 SILICONE/CARBON FILLED
TECKNIT	ADHESIVE CON/RTV-I
	ADHESIVE CON/RTV-II
	ADHESIVE CON/RTV-NI
	ADHESIVE CON/RTV-SC
	ADHESIVE P/N 72-00008
	ADHESIVE TECHKIT TS118-6
	ADHESIVE TECKBOND 72-00119
	ADHESIVE TECKBOND 72-00125
	FABRIC TECKNIT 72-00008 FLEX CONDUCTIVE EPOXY S.F.
	FABRIC TECKNIT 72-00014
	FABRIC TECKNIT 72-08116AG FILL
	FABRIC TECKNIT 77-09-776
	RUBBER CONSIL 2 SILICONE/AG FILLED
	RUBBER CONSIL C875 CONDUCTIVE FLUOROSILICONE
	RUBBER CONSIL R HT
	RUBBER CONSIL R854 CONDUCTIVE FLUOROSILICONE
	RUBBER SILICONE RTV 1/SILVER
	RUBBER VULCON CL 1 GR 40 T2
	RUBBER VULCON CL 2 GR 40
	RUBBER VULCON SILICONE
TEIJIN-KASEI CO	POLYCARBONATE PANLITE L1250
TEIKOKU SEN-I CO	FABRIC STRAP CONTAINER COVER ND-3010 C/#1
TEKNIT INC	GASKET TECK SPAN P/N 48-09860
TEKTRONIX	LAMIN EPOXY/GLASS PC BOARD
TELATEMP CORP	FILM TEMP SENSOR 110X
TELE-MEASUREMENTS	COATING ENAMEL WHITE
	COATING SYNKOTE 71976 BLUE
TELECTNET	WIRE ELEC HEADSET 28 AWG
TELEDYNE BROWN ENG	COATING CONVERSION CHROMATE
	COATING URETHANE ON 1/16 AL FOIL
	LABEL IDENTIFICATION
	RUBBER SILICONE TSC11
	WIRE ELEC TEFLON TFE
	YARN POLYESTER 1100 DENIER
TELEDYNE THERMATICS	WIRE ELEC ETFE TEFZEL
	WIRE ELEC FEP/POLYIMIDE TAPE
	WIRE ELEC PVC-A
	WIRE ELEC TEFLON PFA

MSFC-HDBK-527 REV F 9999942 0006959 9

Information Handling Services, 2000

NON-METALS DESIGNATIONS BY MANUFACTURER

MANUFACTURER	DESIGNATION
TELEDYNE THERMATICS	WIRE ELEC WITH METAL BRAID SHIELD
TELEFLEX INC	COATING SERMETEL TW
TEMPIL	LABEL TEMPILABEL 4D-150/66
	LABEL TEMPILABEL 8D-210/99
TEMPO PAINT AND VARNISH	COATING BLACK 37038 POLYAMIDE EPOXY
	COATING GRAY 36231 POLYAMIDE EPOXY
	COATING POLYAMIDE EPOXY
TENNECO	INSULATION FOAM DENSITE 2
	INSULATION FOAM DENSITE 2 POLYESTER URETHANE 5
	INSULATION FOAM DENSITE 3
	INSULATION FOAM DENSITE EN-3 POLYETHER
	INSULATION FOAM TENNECO 6LBN BLACK
TENNESSE VALVE	RUBBER VITON FLUID RESISTANT
TENNESSEE VALLEY	RUBBER VITON FLUID RESISTANT
TENSOLITE	CABLE COAXIAL TFE/FEP
	HARNESS TENSOLITE ASSEMBLY 20AWC
	WIRE ELEC
	WIRE ELEC TEFLON TFE
TERRELL CORP	ADHESIVE TERLAN 1580 POLYIMIDE
TESCOM CORP	KEL-F 81
	SEALANT TEFLON NOC
	TEFLON TFE VIRGIN
	TEFLON TFE/15% GRAPHITE
TESTWORTH LABS	ADHESIVE PARALAC DPB278
	ADHESIVE PARALAC RC57
	ADHESIVE SH238
TETKO INC	FABRIC POLYESTER FILTER
	NYLON NITEX HC3-20 MONOFILAMEN
TETRAFLUOR	PLASTIC TETRAFLUOR TF619
	PLASTIC TETRAFLUOR TFC021
	PLASTIC TETRAFLUOR TFC025
	PLASTIC TETRAFLUOR TFC030
	PLASTIC TETRAFLUOR TFC031
	PLASTIC TETRAFLUOR TFC033
	PLASTIC TETRAFLUOR TFC045
	PLASTIC TETRAFLUOR TFC082
	PLASTIC TETRAFLUOR TFC086
	PLASTIC TETRAFLUOR TFC108
	PLASTIC TETRAFLUOR TFC608
	PLASTIC TETRAFLUOR TFC616
	PLASTIC TETRAFLUOR TFC617
	PLASTIC TETRAFLUOR TFC618
	PLASTIC TETRALON
	PLASTIC TETRALON 510
	PLASTIC TETRALON 710
	PLASTIC TETRALON TFC031
	PLASTIC TETRALON TFC033
	TETRALON TF 403-017
TEX-TECH IND	FABRIC GLASS/NOMEX S2283R
TEXACO	LUBE GREASE UNITEMP 500
TEXACO OIL	LUBE RB-PREMIUM
TEXAPOL	PLASTIC TEXALON 1106A
	PLASTIC TEXALON 1108A
	PLASTIC TEXALON 1110 AL PL2 HS BK18
TEXAPOL	PLASTIC TEXALON 1200A
	PLASTIC TEXALON 1200A FR
	PLASTIC TEXALON 1200A HS
	PLASTIC TEXALON 1200A ZIP
	PLASTIC TEXALON 1200A ZIP 10
	PLASTIC TEXALON 1200A ZIP 10 BX11
	PLASTIC TEXALON 1203D ZIP 10
	PLASTIC TEXALON 1308A
	PLASTIC TEXALON 1310
	PLASTIC TEXALON 600A
	PLASTIC TEXALON 600A HS
	PLASTIC TEXALON 600A HV HS
	PLASTIC TEXALON 600A PL2
	PLASTIC TEXALON 600A ZIP
	PLASTIC TEXALON 600A ZIP 10
	PLASTIC TEXALON 623 HS BK13
	PLASTIC TEXALON 680A
	PLASTIC TEXALON GF 1200 A33
	PLASTIC TEXALON GF 1308 A13
	PLASTIC TEXALON GF 1310-13
	PLASTIC TEXALON GF 600 A33
	PLASTIC TEXALON GMF 600-40
	PLASTIC TEXALON MF 1200A-40
	PLASTIC TEXALON MF 1200A1-40
	PLASTIC TEXALON MF 600-40
	PLASTIC TEXALON XP1296
	PLASTIC TEXALON XP1317
	PLASTIC TEXALON XP1319 HS
TEXAS REFINERY CORP	GREASE STERATE HYDROXYLIC CA12
TEXAS TECH UNIV	FABRIC DACRON S1185/FORM A
	FABRIC DACRON S1185/FORM B
	FABRIC DACRON S1185/FORM C
TEXAS URETHANE	INSULATION FOAM POLYURETHANE FSC8BA55 P-2
	INSULATION FOAM POLYURETHANE P4
	INSULATION FOAM POLYURETHANE TEXAS 407-22
	INSULATION FOAM TEXTHANE 2000-24 ISOCYANAU
	INSULATION FOAM TEXTHANE 221-25
	POLYURETHANE
	INSULATION FOAM TU28 URETHANE
	INSULATION FOAM TU32 URETHANE
	INSULATION FOAM TX39 URETHANE
	INSULATION FOAM TX43 URETHANE
	INSULATION FOAM URETHANE
TEXTRON	ZIPPER NOMEX/BRASS
TFE INDUSTRIES	PLASTIC ROD METHACRYLATE
THERMAL MATERIALS	INSULATION SILFRAY CERAMIC
THERMAL SCIENCES INC	THERMAL LAG FR MATERIAL
THERMALLOY	ADHESIVE THERMAL 4952 EPOXY
	ADHESIVE THERMALBOND
	COMPOUND THERMACOTE BLUE POLYBUTENE
	COMPOUND THERMACOTE NOC SILICONE
	COMPOUND THERMACOTE PINK
	COMPOUND THERMACOTE POLYBUTENE
	FILM THERMOFILM 4500-5
	LUBE GREASE THERMAL JOINT CPD

MSFC-HDBK-527 REV F ■ 9999942 0006960 5 ■

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
THERMALLOY	LUBE GREASE THERMOCOTE 250
	MOLD COMPOUND DAP SDG 7717
	MOLD COMPOUND GLASS FILL 7721-3PPS
THERMAX WIRE CORP	CABLE 77 OHM TWINAX
	WIRE ELEC ETFE WHT 20 AWG
THERMECH ENGINEERING	COATING FEP
	KEL-F 81
	KEL-F CTFE UNPLASTICIZED
	TECFLUORFIL B TFE/11% METAL OX
	TECHFLUORIL TFE/GRAPH CG-11
	TEFLON FEP
	TEFLON TFE VIRGIN
	TEFLON TFE/25% GLASS
THERMO COTE	COATING PROTEXOCOTE M70
THERMOELECTRIC	CONNECTOR P/N 41203 PHENOLIC
THERMOFIL	PLASTIC THERMOFIL A 20FG0100
	PLASTIC THERMOFIL A 35FG0100
	PLASTIC THERMOFIL A1 20FG0570
	PLASTIC THERMOFIL A1 20FG0700
	PLASTIC THERMOFIL B 20FG0100
	PLASTIC THERMOFIL B 35FB0100
	PLASTIC THERMOFIL B 35FG0100
	PLASTIC THERMOFIL D 10FG0100
	PLASTIC THERMOFIL D 20FG0100
	PLASTIC THERMOFIL D 20FG0500
	PLASTIC THERMOFIL D 30FG0100
	PLASTIC THERMOFIL D 9900-6500
	PLASTIC THERMOFIL E 15FG0100
	PLASTIC THERMOFIL E 15FG0590
	PLASTIC THERMOFIL E 30FG0100
	PLASTIC THERMOFIL E 30FG0287
	PLASTIC THERMOFIL E 30FG0590
	PLASTIC THERMOFIL E 30NF0100
	PLASTIC THERMOFIL E 40FG0100
	PLASTIC THERMOFIL E 40MI0100
	PLASTIC THERMOFIL E 45FM0319
	PLASTIC THERMOFIL E 45FM0393
	PLASTIC THERMOFIL E 9900-0590
	PLASTIC THERMOFIL E1 10FG0100
	PLASTIC THERMOFIL E1 30FG0100
	PLASTIC THERMOFIL E1 30FG0584
	PLASTIC THERMOFIL E2 30FG0100/E2 30FG0578
	PLASTIC THERMOFIL E2 30FG7100
	PLASTIC THERMOFIL E2 30NF0100
	PLASTIC THERMOFIL E2 45FM0393
	PLASTIC THERMOFIL E2 55FG0100
	PLASTIC THERMOFIL F 10FG0100
	PLASTIC THERMOFIL F 30FG0100
	PLASTIC THERMOFIL G 20FG0214
	PLASTIC THERMOFIL G 20NF0100
	PLASTIC THERMOFIL G 30FG0100
	PLASTIC THERMOFIL G 900-0257
	PLASTIC THERMOFIL G 9900-0215
	PLASTIC THERMOFIL K 20FG0100
	PLASTIC THERMOFIL K 30FG0100
THERMOFIL	PLASTIC THERMOFIL K 30FG0214
	PLASTIC THERMOFIL K 30NF0100
	PLASTIC THERMOFIL K2 30FG0100
	PLASTIC THERMOFIL K2 30NF0100
	PLASTIC THERMOFIL L 20FG0100
	PLASTIC THERMOFIL L 30FG0100
	PLASTIC THERMOFIL L1 30FG0580
	PLASTIC THERMOFIL N 15FG0100
	PLASTIC THERMOFIL N 15FG0500
	PLASTIC THERMOFIL N 30FG0100
	PLASTIC THERMOFIL N 30FG0214
	PLASTIC THERMOFIL N 30FG0500
	PLASTIC THERMOFIL N 30NF0100
	PLASTIC THERMOFIL N 40BG0100
	PLASTIC THERMOFIL N 40FM0100
	PLASTIC THERMOFIL N 40MF0100
	PLASTIC THERMOFIL N 9900-0500
	PLASTIC THERMOFIL N11 30FG0100
	PLASTIC THERMOFIL N11 30NF0100
	PLASTIC THERMOFIL N11 40MF0350
	PLASTIC THERMOFIL N12 30FG0100
	PLASTIC THERMOFIL N12 30FG0282
	PLASTIC THERMOFIL N12 30FG0500
	PLASTIC THERMOFIL N12 30NF0100
	PLASTIC THERMOFIL N3 13FG0100
	PLASTIC THERMOFIL N3 13FG0700
	PLASTIC THERMOFIL N3 15FG0560
	PLASTIC THERMOFIL N3 20NF0100
	PLASTIC THERMOFIL N3 30FG0214
	PLASTIC THERMOFIL N3 30FG0231
	PLASTIC THERMOFIL N3 30FG0560
	PLASTIC THERMOFIL N3 30FR0282
	PLASTIC THERMOFIL N3 30NF0214
	PLASTIC THERMOFIL N3 33FG0100
	PLASTIC THERMOFIL N3 33FG0700
	PLASTIC THERMOFIL N3 35FM0310
	PLASTIC THERMOFIL N3 40MF0350
	PLASTIC THERMOFIL N3 40MF8300
	PLASTIC THERMOFIL N3 40NF0100
	PLASTIC THERMOFIL N3 43FG0100
	PLASTIC THERMOFIL N3 9900-0200
	PLASTIC THERMOFIL N3 9900-0214
	PLASTIC THERMOFIL N3 9900-0231
	PLASTIC THERMOFIL N3 9900-0279
	PLASTIC THERMOFIL N3 9900-0560
	PLASTIC THERMOFIL N5 15FG0100
	PLASTIC THERMOFIL N5 30FG0100
	PLASTIC THERMOFIL N6 30FG0100
	PLASTIC THERMOFIL N6 30FG0214
	PLASTIC THERMOFIL N6 30FG0282
	PLASTIC THERMOFIL N6 30FG0500
	PLASTIC THERMOFIL N6 30NF0100
	PLASTIC THERMOFIL N6 9900-0500
	PLASTIC THERMOFIL N7 13FG0100
	PLASTIC THERMOFIL N7 20FG0500

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
THERMOFIL	PLASTIC THERMOFIL N7 20NF0100
	PLASTIC THERMOFIL N7 30FG0100
	PLASTIC THERMOFIL N7 35MF7365
	PLASTIC THERMOFIL N7 9900-0500
	PLASTIC THERMOFIL N8 30FG0100
	PLASTIC THERMOFIL N9 30FG0100
	PLASTIC THERMOFIL P 10FG0100
	PLASTIC THERMOFIL P 20FG0100
	PLASTIC THERMOFIL P 20FG0500
	PLASTIC THERMOFIL P 20FG0720
	PLASTIC THERMOFIL P 20MF0500
	PLASTIC THERMOFIL P 20MI0100
	PLASTIC THERMOFIL P 30FG0100
	PLASTIC THERMOFIL P 40CC0100
	PLASTIC THERMOFIL P 40CC0720
	PLASTIC THERMOFIL P 40MI0100
	PLASTIC THERMOFIL P 40MI0720
	PLASTIC THERMOFIL P 40TC0100
	PLASTIC THERMOFIL P 9900-0500
	PLASTIC THERMOFIL P 9900-0570
	PLASTIC THERMOFIL P1 10FG0100
	PLASTIC THERMOFIL P1 20FG0100
	PLASTIC THERMOFIL P1 20FG0720
	PLASTIC THERMOFIL P1 30FG0100
	PLASTIC THERMOFIL P6 10FG0100
	PLASTIC THERMOFIL P6 20FG0100
	PLASTIC THERMOFIL P6 20FG0500
	PLASTIC THERMOFIL P6 20FG0570
	PLASTIC THERMOFIL P6 30FG0100
	PLASTIC THERMOFIL P6 30FG0720
	PLASTIC THERMOFIL R 10FG0100
	PLASTIC THERMOFIL R 10FG0568
	PLASTIC THERMOFIL R 20NF0214
	PLASTIC THERMOFIL R 30FG0100
	PLASTIC THERMOFIL R 30FG0214
	PLASTIC THERMOFIL R 30FG0568
	PLASTIC THERMOFIL R 40NF0100
	PLASTIC THERMOFIL R 9900-0200
	PLASTIC THERMOFIL R 9900-0214
	PLASTIC THERMOFIL R2 10FG0100
	PLASTIC THERMOFIL R2 30FG0100
	PLASTIC THERMOFIL S 20FG0100
	PLASTIC THERMOFIL S 30FG0214
	PLASTIC THERMOFIL S 30MF0360
	PLASTIC THERMOFIL S 30NF0100
	PLASTIC THERMOFIL S 40FG0100
	PLASTIC THERMOFIL T 20NF0100
	PLASTIC THERMOFIL T 30FG0214
	PLASTIC THERMOFIL T 30NF0214
	PLASTIC THERMOFIL T 40FG0100
	PLASTIC THERMOFIL T 40NF0100
	PLASTIC THERMOFIL T 40NG0948
	PLASTIC THERMOFIL T 50CG0940
	PLASTIC THERMOFIL T 50FM0100
	PLASTIC THERMOFIL U 10FG0100
THERMOFIL	PLASTIC THERMOFIL V 10FG0100
	PLASTIC THERMOFIL V 20FG0100
	PLASTIC THERMOFIL V 30FG0100
	PLASTIC THERMOFIL W 10FG0100
	PLASTIC THERMOFIL W 30FG0100
	PLASTIC THERMOFIL W 30NF0100
	PLASTIC THERMOFIL W 30NF0214
	PLASTIC THERMOFIL Y 20FG0100
	PLASTIC THERMOFIL Y 20FG0500
	PLASTIC THERMOFIL Y7 9900-6500
THERMOSET PLASTICS	ADHESIVE 322 EPOXY
	ADHESIVE THERMOSET 100
	ADHESIVE THERMOSET 101
	ADHESIVE THERMOSET 103
	ADHESIVE THERMOSET 104
	ADHESIVE THERMOSET 125
	ADHESIVE THERMOSET 267
	ADHESIVE THERMOSET DC232
	ADHESIVE THERMOSET DC80
	ADHESIVE THERMOSET EP233
	ADHESIVE THERMOSET EP280
	ADHESIVE THERMOSET EP433
	ADHESIVE THERMOSET EP539
	ADHESIVE THERMOSET EP548
	ADHESIVE THERMOSET EP598
THIOKOL	ADHESIVE CERAMIC TYCEMENT UF3206
	ADHESIVE CERAMIC TYCEMENT UF3242
	ADHESIVE RUBBER NBR/MEK
	COATING SOLITHANE 113/300
	COATING SOLITHANE 113/300/CABOSIL
	COATING SOLITHANE C113-300/DC3140
	INK DYNACURE LETTERING
	LAMIN EPOXY/GLASS/SOLITHANE COATED
	PROPELLANT LINER UF2137
	PROPELLANT TPH1148
	PROPELLANT TPH1154
	SEALANT UF3195
	TAPE SCOTCH 53 POLYURETHANE/SOLITHANE 113/300
THIOKOL/UNION CARBIDE	ADHESIVE STW53215 PRIMER WITH A187 XYLENE COUPLING AGENT
THOMAS & BATTS	ADHESIVE LOCTITE 747-56
THOMAS & BETTS	CABLE TIES MOUNT TC103 NYLON
	CABLE TIES TEFZEL TY-RAP TYZ
	CABLE TIES TY-27M NYLON
	CABLE TIES TY-28M NYLON
	SEALANT ZINC/GREASE 21059
	SPLICES NYLON STA-KON
THOMAS TAYLOR & SONS	CORD ELASTIC RUBBER/KEVLAR/COTTON
THREEBOND OF AMERICA	ADHESIVE THREE SEALING COMPOUND
THURLOW GLOVE CO	LEATHER DEERSKIN
TIGERS POLYMER CORP	RUBBER SILICONE SR50
TIME ELECTRONIC WEST	CONNECTOR ELECTRICAL
TIMES FIBER	CABLE ELECTRICAL 07145 AG COATED CU WITH TEFLON AND ALUMINIZED MYLAR

MSFC-HDBK-527 REV F 9999942 0006962 9

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
TIMES FIBER	WIRE ELEC FEP WITH POLYIMIDE TAPE
	WIRE ELEC MD 913 FLUOROCARBON POLYIMIDE INSULATION
	WIRE ELEC POLYIMIDE INSULATION
TIMES MIRROR CO	TAPE CHARTPAK GRAPHIC 5003 BLUE
	TAPE CHARTPAK GRAPHIC 5005 ORANGE
	TAPE CHARTPAK GRAPHIC 5014 PS BROWN
	TAPE CHARTPAK GRAPHIC 5017 GREEN
TIMES WIRE & CABLE	CABLE COAX RG188
	WIRE ELEC PVC-A
TIODIZE	LUBE DRY TIOLUBE 1175 INORGANIC
	LUBE DRY TIOLUBE 460 MS21063
TITEFLEX	HOSE ASSEMBLY TITEFLEX R270-4
	HOSE FLEX ASSEMBLY/FIRE SLEEVING
	HOSE LINER FLEX TFE/25% CARBON
	HOSE LINER PTFE
	HOSE PLSS FLEX TEFLON LINED
	HOSE R267/410 SERIES
	HOSE TITEFLEX CONDUCTIVE
	SLEEVING NOMEX BRAID
TOAGOSEI CHEMICAL	ADHESIVE ARON ALPHA 202
TOHO RAYON CO	FABRIC PYROMEX A-201
TOHOKU KINZOKU	MAGNETIC CORE T12-125
TORAY	FILM LUMILOR POLYESTER INSULATION
	LUBE GREASE HIGH VACUUM SILICONE
	LUBE GREASE SH340
TOSHIBA	VARNISH INPREGNATION IMIDALLOY TVB 2705
TOYOTA	MOLD COMPOUND POLY-ACETAL
	MOLD COMPOUND POLYETHYLENE
TRA-CON INC	ADHESIVE BIPAX TRADUCT BB2902
	ADHESIVE TRABOND 2101
	ADHESIVE TRABOND 2106
	ADHESIVE TRABOND 2106T
	ADHESIVE TRABOND 2111
	ADHESIVE TRABOND 2113
	ADHESIVE TRABOND 2114
	ADHESIVE TRABOND 2115
	ADHESIVE TRABOND 2122
	ADHESIVE TRABOND 2123
	ADHESIVE TRABOND 2124
	ADHESIVE TRABOND 2125
	ADHESIVE TRABOND 2126
	ADHESIVE TRABOND 2129
	ADHESIVE TRABOND 2130
	ADHESIVE TRABOND 2132
	ADHESIVE TRABOND 2133
	ADHESIVE TRABOND 21350
	ADHESIVE TRABOND 2143D
	ADHESIVE TRABOND 2147
	ADHESIVE TRABOND 2151
	ADHESIVE TRABOND 2161
	ADHESIVE TRABOND 21620
	ADHESIVE TRABOND 2165
	ADHESIVE TRABOND 2190
	ADHESIVE TRABOND 2202
TRA-CON INC	ADHESIVE TRABOND 2203
	ADHESIVE TRABOND 2208
	ADHESIVE TRABOND 2211
	ADHESIVE TRABOND 2212
	ADHESIVE TRABOND 2215
	ADHESIVE TRABOND 2225
	ADHESIVE TRABOND 2230
	ADHESIVE TRABOND 2248
	ADHESIVE TRABOND 2254
	ADHESIVE TRABOND BB2112
	ADHESIVE TRABOND BB2116
	ADHESIVE TRABOND F1130F117
	ADHESIVE TRABOND KSNA
	ADHESIVE TRADUCT 2924
TRAIL CHEMICAL CORP	COATING LACQUER BLACK 32178-66
	COATING X75207-66 EPOXY/ENAMEL
TRANSENE	ADHESIVE A PRIMER
	ADHESIVE EPOXY 10
	ADHESIVE EPOXY 11
	ADHESIVE EPOXY 12
	ADHESIVE EPOXY 13
	ADHESIVE EPOXY 14
	ADHESIVE EPOXY 15
	ADHESIVE EPOXY 16
	ADHESIVE EPOXY 17
	ADHESIVE EPOXY 20
	ADHESIVE EPOXY 30
	ADHESIVE EPOXY 50
	ADHESIVE EPOXY 850
	ADHESIVE EPOXY BOND ADHESIVE
	ADHESIVE GE10
	ADHESIVE GE20
	ADHESIVE GE30
	ADHESIVE GE40
	ADHESIVE MICROCIRCUIT SILVER TYPE K
	ADHESIVE MICROCIRCUIT SILVER TYPE L
	ADHESIVE MICROCIRCUIT SILVER TYPE N
	ADHESIVE MICROCIRCUIT SILVER TYPE O
	ADHESIVE NICKEL BOND TYPE 40
	ADHESIVE NICKEL BOND TYPE 50
	ADHESIVE NICKEL BOND TYPE 60
	ADHESIVE SILVER BOND TYPE 40
	ADHESIVE SILVER BOND TYPE 50
	ADHESIVE SILVER BOND TYPE 60
	ADHESIVE SILVER EPOXY PASTE TYPE 1 AND 2
	ADHESIVE SILVERBOND CONDUCTIVE
	ADHESIVE SMA100
	ADHESIVE SMA1600
	ADHESIVE SMA200
	ADHESIVE SMA300
	ADHESIVE SMA400
	ADHESIVE SMA500
	ADHESIVE SMA600
	ADHESIVE THERMASIL 1 MODIFIED
	ADHESIVE THERMASIL T2/CS

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
TRANSENE	ADHESIVE TRANSEAL 1175T
	ADHESIVE TRANSENE PDA D500
	ADHESIVE TRANSENE PDA S500
	PLASTIC POLY-CLEAR
	RUBBER MBS106
	RUBBER MBS154
TRANSITRON	GROMMET NEOPRENE
TRANSLUBE INC	LUBE DRY TRANSLUBE 20204
TRANSTEAM	KEYBOARD COMPUTERWISE TT1A
TRAVIS MILLS	FABRIC NOMEX 0049 6OZ FP/WP
	FABRIC NOMEX ARAMID 3/0049 6OZ
TREVARNO DIVISION	FABRIC GLASS/POLYESTER F149 IMPREG
TRIBOL INDUSTRIES	SEALANT TRIBOLON PI101 POLYIMIDE
TRIDOX CORP	POTTING COMPOUND TRIDOX F88 EPOXY
TROMPETER	CONNECTOR ELECTRICAL
TRW	CLAMP NYLON
	INSULATION BLANKET MIN-K FAB/STEEL
	RUBBER AF-E332 EPR
	RUBBER EPR AF-E411
	TEFLON TFE VIRGIN
TUBBS CORDAGE	CORD SILVERTON 55-1 ORANGE
TUCK INDUSTRIES	TAPE 58
	TAPE FES51 ALUMINUM GLASS WITH SILICONE ADHESIVE
	TAPE MYLAR 49/SILICONE
	TAPE PS ADHESIVE
	TAPE VINYL/COTTON TUCK 91B
TULSA DIV	LAMIN EPOXY/NOMEX R398/F263
	RUBBER SILICONE CL 1A & 1B GR 50
TURCO PROD	COATING MXSA/TURCO T6109/AL(OH)3
	COATING MXSA/TURCO T6109/MG(OH)2
	COATING MXSA/TURCO T6109/OXALIC
	COATING MXSA/TURCOT6109/HYP H2200
	COATING TURCO T6094 BLACK
	COATING TURCO T6109 WHITE
	COATING TURCO T6109/ELECTRODAY 500
	CORK B-STAGED/COATING TURCO T6109
	CORK P50/COATING TURCO T6109
	MSA-1/TURCO T6109 TOPCOAT
TYROLIT CORP	COATING TYROLIT #GED-0 OPTICAL
U O PRODUCTS	LAMIN EPOXY/GLASS
	LAMIN EPOXY/GLASS/URALANE 5750 COATED
	LAMIN EPOXY/GLASS/URALANE 5753 COATED
U S COATINGS	COATING URETHANE ASMBY
U S GRAPHITE	GRAPHITAR G36-295
	GRAPHITAR GRADE 14
	GRAPHITAR GRADE 30A
	GRAPHITE LUBE
	SEALANT GRAPHITAR 114/CARBON
	SEALANT GRAPHITAR 39/CARBON FACE
	SEALANT GRAPHITAR 86/CARBON
U S PAINT LACQUER & CHEM	COATING ZINC CHROMATE
U S POLYMERIC	ADHESIVE EPOXY XA924-40/E793
	ADHESIVE NEOPRENE 61015
U S POLYMERIC	COATING E755G EPOXY
	DUCT E-720-E FR/120/MBO125-070
	INSULATION LAMINATE E7023-1581
	LAMIN EPOXY/GLASS
	LAMIN EPOXY/GLASS 7781/550/P650M
	LAMIN EPOXY/GLASS E720E/7581 FR
	LAMIN EPOXY/GLASS E747/VOLAN/1581
	LAMIN EPOXY/GRAPHITE GY70/E42
	LAMIN EPOXY/KELVAR E707/KEVLAR 120
	LAMIN EPOXY/KEVLAR E42
	LAMIN EPOXY/KEVLAR E719/12 KEVLAR 181
	LAMIN EPOXY/KEVLAR E720E FR 49-120
	LAMIN FIBERITE MX2652
	LAMIN FIBERITE MX4926
	LAMIN FIBERITE MXB6020
	LAMIN FM5055 CARBON PHENOLIC
	LAMIN KEVLAR 143/E788
	LAMIN PHENOLIC/GLASS F508 VOLAN A/7781
	LAMIN/EPOXY/KEVLAR E720FR/KEVLAR 49-181
	MOLD COMPOUND DAP SDG 6120
	TEFLON TFE VIRGIN
U S STEEL	PLASTIC USS C040Y
	PLASTIC USS C120Y
	PLASTIC USS C432-12
	PLASTIC USS C432-4
	PLASTIC USS CP350A
	PLASTIC USS CP450A
	PLASTIC USS CR080A
	PLASTIC USS CRVO-8
	PLASTIC USS D007W
	PLASTIC USS F007
	PLASTIC USS F010M
	PLASTIC USS F012
	PLASTIC USS F012M
	PLASTIC USS F015
	PLASTIC USS F040F
	PLASTIC USS F080F
	PLASTIC USS F080L
	PLASTIC USS F1202L
	PLASTIC USS F120F
	PLASTIC USS F120L
	PLASTIC USS FP120F
	PLASTIC USS FP200F
	PLASTIC USS FP300F
	PLASTIC USS FP330W
	PLASTIC USS FPT120F
	PLASTIC USS FPT180F
	PLASTIC USS FPT230F
	PLASTIC USS FPT350F
	PLASTIC USS FT040W
	PLASTIC USS FT120C
	PLASTIC USS FT120W
	PLASTIC USS FT120W2L
	PLASTIC USS FT120WB
	PLASTIC USS FT145V

MSFC-HDBK-527 REV F 9999942 0006964 2

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
U S STEEL	PLASTIC USS L040G
	PLASTIC USS T14025G
	PLASTIC USS T14040G
	PLASTIC USS T14070G
	PLASTIC USS T14230G
	PLASTIC USS T15035G
	PLASTIC USS T15230G
	PLASTIC USSS FT080W
UAH	CAST CAROPLASTIC PROPOSED FOR PPE
UBE INDUSTRIES	PLASSTIC UBE NYLON 5013B
	PLASTIC UBE NYLON 1011FB
	PLASTIC UBE NYLON 1011GC4
	PLASTIC UBE NYLON 1013B
	PLASTIC UBE NYLON 1013NB
	PLASTIC UBE NYLON 1013NH
	PLASTIC UBE NYLON 1013NU2
	PLASTIC UBE NYLON 1013NW8
	PLASTIC UBE NYLON 1013R
	PLASTIC UBE NYLON 1013RU1
	PLASTIC UBE NYLON 1013RW
	PLASTIC UBE NYLON 1015G1
	PLASTIC UBE NYLON 1015GC6
	PLASTIC UBE NYLON 1015GC9
	PLASTIC UBE NYLON 10181
	PLASTIC UBE NYLON 1022B
	PLASTIC UBE NYLON 1022SV2
	PLASTIC UBE NYLON 1030B
	PLASTIC UBE NYLON 1030J
	PLASTIC UBE NYLON 1030QB
	PLASTIC UBE NYLON 2015B
	PLASTIC UBE NYLON 2015SV
	PLASTIC UBE NYLON 2020B
	PLASTIC UBE NYLON 2020GC4
	PLASTIC UBE NYLON 2020GC6
	PLASTIC UBE NYLON 2020GC9
	PLASTIC UBE NYLON 2020U
	PLASTIC UBE NYLON 2020UW1
	PLASTIC UBE NYLON 3014U
	PLASTIC UBE NYLON 3020LU1
	PLASTIC UBE NYLON 3024LU
	PLASTIC UBE NYLON 3024U
	PLASTIC UBE NYLON 3030GCU
	PLASTIC UBE NYLON 3030H
	PLASTIC UBE NYLON 3035JL1
	PLASTIC UBE NYLON 3035JU
	PLASTIC UBE NYLON 3035JU6
	PLASTIC UBE NYLON 3035LU
	PLASTIC UBE NYLON 3035U
	PLASTIC UBE NYLON 5033J12
	PLASTIC UBE NYLON UMC1
UBS CHEM	ADHESIVE AF770
	ADHESIVE UR1087 VINYL/URETHANE
UMPCO	CLAMP CUSHION FLOUROSILICONE
	CLAMP CUSHION SILICONE/FIBERGLASS CL 3B GR 60
UMPCO	FABRIC SILICONE/GLASS
UNI-GLAZE	COATING C12546 EPOXY
UNI-MARK	INK UNIMARK 960/JPC K10 PAPER
	PEN UNIMARK 960
UNIFORM TUBES	CABLE COAXIAL TFE/FEP
UNION 76	ADHESIVE AMSCO RES 19BR64
	ADHESIVE AMSCO RES 19RB64P
	ADHESIVE AMSCO RES 202A
	ADHESIVE AMSCO RES 202AH
	ADHESIVE AMSCO RES 202AM
	ADHESIVE AMSCO RES 3001
	ADHESIVE AMSCO RES 3001P
	ADHESIVE AMSCO RES 3004
	ADHESIVE AMSCO RES 3008
	ADHESIVE AMSCO RES 3034
	ADHESIVE AMSCO RES 3063
	ADHESIVE AMSCO RES 3151
	ADHESIVE AMSCO RES 4000
	ADHESIVE AMSCO RES 4000 (50/50)
	ADHESIVE AMSCO RES 4001
	ADHESIVE AMSCO RES 4040
	ADHESIVE AMSCO RES 4072
	ADHESIVE AMSCO RES 4104 (65/35)
	ADHESIVE AMSCO RES 5007
	ADHESIVE AMSCO RES 528
	ADHESIVE AMSCO RES 542
	ADHESIVE AMSCO RES 546
	ADHESIVE AMSCO RES 6038
	ADHESIVE AMSCO RES 6105 (45/55)
	ADHESIVE AMSCO RES 6130 (HS/SS)
	ADHESIVE AMSCO RES 6150 (45/55)
	ADHESIVE AMSCO RES 6206
	ADHESIVE AMSCO RES 6213
	ADHESIVE AMSCO RES 6221
	ADHESIVE AMSCO RES 6222
	ADHESIVE AMSCO RES 6247
	ADHESIVE AMSCO RES 6255
	ADHESIVE AMSCO RES 6272
	ADHESIVE AMSCO RES 7200
	ADHESIVE AMSCO RES 8795
	ADHESIVE AMSCO RES 9000
	ADHESIVE AMSCO RES 9001
	ADHESIVE AMSCO RES 9102
	ADHESIVE AMSCO RES 9105
	ADHESIVE AMSCO RES 9201
	ADHESIVE AMSCO RES 9202
	ADHESIVE AMSCO RES 9202V60
	ADHESIVE AMSCO RES 9204
	ADHESIVE AMSCO RES 9205
	ADHESIVE AMSCO RES 9211
	ADHESIVE AMSCO RES 9213
	ADHESIVE AMSCO RES 9214
	ADHESIVE AMSCO RES 9218
	ADHESIVE AMSCO RES 930
	ADHESIVE AMSCO RES 931

MSFC-HDBK-527 REV F 9999942 0006965 4

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
UNION 76	ADHESIVE AMSCO RES 940
	ADHESIVE AMSCO RES 9621
	ADHESIVE AMSCO RES 9622
	ADHESIVE AMSCO RES M3153
	ADHESIVE AMSCO RES P528F
	ADHESIVE AMSCO RES P546
	ADHESIVE AMSCO RES S55
UNION CARBIDE	BATTERY EVERREADY ENERGIZER E91 SIZE AA
	CARBON GRAPHITE MOLD MECH
	CARBON GRAPHITE PUREBOND P9193
	COATING ENVIBAR UV1244T
	COATING EPOXY ERLX1964/1527426SPQ
	COATING PARYLENE D
	GRAPHITE ATJ
	GRAPHITE BAR/100% GRAFOIL
	GRAPHITE G3418 GR GTB GRAFOIL
	GRAPHITE GR-GTA/GRAFOIL
	MICROFALLONS PHENOLIC
	MOLD COMPOUND BAKELITE
	MOLD COMPOUND POLYSULFONE P-1720
	PLASTIC BAKELITE DPD6169 NATURAL
	PLASTIC BAKELITE DPDA6479 NATURAL
	PLASTIC BAKELITE DQDA6479 NATURAL 7
	PLASTIC BAKELITE DQDA6480 NATURAL 7
	PLASTIC BAKELITE OPDA9169 NATURAL
	PLASTIC DBDA0160 NATURAL
	PLASTIC DFD4960 NATURAL
	PLASTIC DFD6005 NATURAL
	PLASTIC DFD6201 NATURAL
	PLASTIC DFDA0588 BLACK 9865
	PLASTIC DFDA4964 NATURAL
	PLASTIC DFDA6059 BLACK 9865
	PLASTIC DFDA6080 BLACK 4865
	PLASTIC DFDA6202 NATURAL
	PLASTIC DFDA6423 BLACK 9865
	PLASTIC DFDA6425 BLACK 9865
	PLASTIC DFDA7540 NATURAL
	PLASTIC DFNF0092 BLACK
	PLASTIC DGDA2400
	PLASTIC DGDA2483 BLACK 4865
	PLASTIC DGDA3485 NATURAL
	PLASTIC DGDB2480 BLACK 4865
	PLASTIC DGDB3110 NATURAL
	PLASTIC DGDJ3364 NATURAL
	PLASTIC DGDJ3479 BLACK 9865
	PLASTIC DHDA2463 BLACK 4865
	PLASTIC DHDA6497 BLACK 9865
	PLASTIC DHDA7704 BLACK 55
	PLASTIC DMDA6010 NATURAL
	PLASTIC DMDA6020 NATURAL 7
	PLASTIC DMDA6143 NATURAL 7
	PLASTIC DMDA6145 NATURAL 7
	PLASTIC DMDA6147 NATURAL 7
	PLASTIC DMDA7154 NATURAL 7UV
	PLASTIC DMDA8920 NATURAL 7
UNION CARBIDE	PLASTIC DMDA8940 NATURAL 7
	PLASTIC DNDA4070 NATURAL 7
	PLASTIC DNDC7148 NATURAL 7
	PLASTIC DNDC7150 NATURAL 7
	PLASTIC DQDA6832 NATURAL 7
	PLASTIC G RESIN 7144 NATURAL 7
	PLASTIC G RESIN 7342 NATURAL 7
	PLASTIC G RESIN 7441 NATURAL 7
	PLASTIC G RESIN 8007 NATURAL 7
	PLASTIC G RESIN 8320 NATURAL 7
	PLASTIC G RESIN 8940 NATURAL 7
	PLASTIC GPEP1000
	PLASTIC GPEP703 NATURAL 7
	PLASTIC GPEP705 NATURAL 7
	PLASTIC GPEP803 NATURAL 7
	PLASTIC GPEP805 NATURAL 7
	PLASTIC GPEP903 BLACK
	PLASTIC GPEP954 NATURAL 7UV
	PLASTIC GPSC2704 BLACK
	PLASTIC GRSN1077 NATURAL 7
	PLASTIC GRSN7147 NATURAL 7
	PLASTIC GRSN7149 NATURAL 7
	PLASTIC GRSN7340 NATURAL 7
	PLASTIC GRSN7341 NATURAL 7
	PLASTIC GRSN7510 NATURAL 7
	PLASTIC GRSN8350 NATURAL 7
	PLASTIC GRSN8907 NATURAL 7
	PLASTIC HFDA0580 BLACK 55
	PLASTIC HFDA0581 BLACK 55
	PLASTIC HFDA0691 BLACK 55
	PLASTIC HFDA5612 BLACK 75
	PLASTIC HFDA5630 BLACK 185
	PLASTIC HFDA6522 NATURAL
	PLASTIC HFDE4201 NATURAL EC
	PLASTIC POLYSULFONE P1700
	PLASTIC POLYSULFONE P1700/P3500
	PLASTIC UCAR DFDA1137 NATURAL
	PLASTIC UCAR DFDA1138 NATURAL
	PLASTIC UDEL POLYSULFONE P1700 CL2611
	RUBBER SILICONE K1203
	SEALANT CDJ83 CARBON PLUS BINDER
	SIEVE MOLECULAR
UNION INK	INK UNIGLAZE C1204 EPOXY
	INK UNIGLAZE C1336 EPOXY BLACK
	INK UNIGLAZE UGLZ8000 BLACK
UNION INSTRUMENT	COMPASS MAGNETIC FSN6605-846-7618
UNION OIL	ADHESIVE 76 RES 6140 (45/55)
	ADHESIVE AMSCO HOT MELT 112
	ADHESIVE AMSCO HOT MELT 233
	ADHESIVE AMSCO HOT MELT 344
UNIROYAL	ADHESIVE SILAPRENE ADHESIVE/SEALANT
	ADHESIVE SILAPRENE ALL WEATHER SEALANT
	ADHESIVE SILAPRENE M6102
	ADHESIVE SILAPRENE M6128
	ADHESIVE SILAPRENE M6130

MSFC-HDBK-527 REV F 9999942 0006966 6

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
UNIROYAL	ADHESIVE SILAPRENE M6164
	ADHESIVE SILAPRENE M6234
	ADHESIVE SILAPRENE M6249
	ADHESIVE SILAPRENE M6272
	ADHESIVE SILAPRENE M6287
	ADHESIVE SILAPRENE M6302
	ADHESIVE SILAPRENE M6303
	ADHESIVE SILAPRENE M6306
	ADHESIVE SILAPRENE M6310
	ADHESIVE SILAPRENE M6314
	ADHESIVE SILAPRENE M6321
	ADHESIVE SILAPRENE M6347
	ADHESIVE SILAPRENE M6378
	ADHESIVE SILAPRENE M644D
	ADHESIVE SILAPRENE M6531
	ADHESIVE SILAPRENE M6562
	ADHESIVE SILAPRENE M6571
	ADHESIVE SILAPRENE M6579
	ADHESIVE SILAPRENE M6587
	ADHESIVE SILAPRENE MS038
	ADHESIVE UNIROYAL 6100
	FABRIC 6007-1-1-54 HEAVY WT
	FABRIC SPACER 6027-1-1
	INSULATION FOAM ENSOLITE TYPE AH
	INSULATION FOAM ENSOLITE TYPE ALF POLYURETHANE
	INSULATION FOAM ENSOLITE TYPE ALG PVC
	LUBE SYNTON PAO 100
	PLASTIC ROYALITE 54
	PLASTIC ROYALITE 57
	POTTING COMPOUND EPON 828/ALUMINUM/TONOX
	SPONGE RUBBER NEOPRENE KOYLON
UNITED FOAM	INSULATION FOAM OMAR100 POLYURETHANE
	INSULATION FOAM POLYURETHANE/POLYESTER 3013
UNITED PAINT MFG	RUBBER DIATHON WATERPROOFING
UNITED STATES RADIUM	RUBBER SILICONE D173-100-12
UNITED TEXTILE	ZIPPER BRASS/COTTON
UNITED WEB	WEBBING POLYESTER ELASTIC
UNITIKA CO	FABRIC UNITIKA 1
UNITRODE	RING PLASTIC ON METAL DIODE
UNIVERSAL CARBON	FABRIC PANOTEX GRAY P-32
UNIVERSAL PRINTING	INK B5749/JCP K10 LITHO-ITEK
UNKNOWN	TAPE MYLAR INS102 ALUMINIZED
UPJOHN	INSULATION FOAM CPR1061 COATED WITH ALBI-COTE FRL WITH COATED SEMICIRCLE
	INSULATION FOAM CPR330-32 POLYISOCYANURATE
	INSULATION FOAM CPR402 POUR
	INSULATION FOAM CPR488/ISOCYANURATE
	INSULATION FOAM CPR920-9-2 POLYURETHANE PS
	INSULATION FOAM CPR920-9-2/HFR2200 PS
	INSULATION FOAM CPR9545 POLYISOCYANURATE
	INSULATION FOAM CPR9700
	INSULATION FOAM CPR9700-1.45S POLYURETHANE

MANUFACTURER	DESIGNATION
UPJOHN	INSULATION FOAM CPR9700-1.75XF POLYURETHANE
	INSULATION FOAM CPR9700-20 POLYURETHANE
	INSULATION FOAM ISOCYANURATE AW255
	INSULATION FOAM POLYCARBODIMIDE
	INSULATION FOAM POLYURETHANE FLEXIBLE
	INSULATION FOAM SLATHANE 821-10
	INSULATION FOAM TEXTHANE 333
	POLYCAST RG256-57-3
URESCO INC	PENETRANT P-545/DEVELOP D-495A
	PENETRANT P-615/DEVELOP D-495A
URETEK	FABRIC ALUMINIZED M11849-5 POLYURETHANE COATED
	FABRIC ALUMINIZED NS452 POLYURETHANE COATED NYLON
	FABRIC ALUMINUM M11481
	FABRIC NS456 ALUMINIZED POLYURETHANE NYLON
	FABRIC NYLON M11480 POLYURETHANE COATED
	FABRIC NYLON URETHANE COATED
	FABRIC NYLON/URETHANE 1111 COATED
	FABRIC NYLON/URETHANE 1414 COATED/ ALUMINIZED AND URESEAL CEMENT
	FABRIC POLYESTER URETHANE COATED
	FABRIC POLYETHER POLYURETHANE COATED NYLON
URETHANE PRODUCTS	INSULATION FOAM POLYURETHANE PHR50
USBI	ABLATOR BTA BOOSTER TROWELLABLE/EC2216/ GLASS SPHERE/CORK
USG INDUSTRIES	RUBBER EPOXICAL 840A
	RUBBER EPOXICAL 885A
USI CHEMICALS	PLASTIC MICROTHENE MP744-16
	PLASTIC MICROTHENE MA778
	PLASTIC MICROTHENE MA795
	PLASTIC MICROTHENE MA795-15
	PLASTIC MICROTHENE MC81035
	PLASTIC MICROTHENE MC91381
	PLASTIC MICROTHENE MK91010
	PLASTIC MICROTHENE MK91018
	PLASTIC MICROTHENE MN 722
	PLASTIC MICROTHENE MN710-20
	PLASTIC MICROTHENE MN711-20
	PLASTIC MICROTHENE MN718
	PLASTIC MICROTHENE MN720-38
	PLASTIC MICROTHENE MP732-16
	PLASTIC MICROTHENE MP736-16
	PLASTIC MICROTHENE MU760 19% VA
	PLASTIC MICROTHENE MU763 9% VA
	PLASTIC NORCHEM
	PLASTIC NORCHEM 1028
	PLASTIC NORCHEM 1028A
	PLASTIC NORCHEM 3010
	PLASTIC NORCHEM 3023
	PLASTIC NORCHEM 3025
	PLASTIC NORCHEM 3029
	PLASTIC NORCHEM 3414
	PLASTIC NORCHEM 5164

MSFC-HDBK-527 REV F 9999942 0006967 8

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
USI CHEMICALS	PLASTIC NORCHEM 5174
	PLASTIC NORCHEM 5304T
	PLASTIC NORCHEM 5305T
	PLASTIC NORCHEM 5307
	PLASTIC NORCHEM 5310T
	PLASTIC NORCHEM 6462HR
	PLASTIC NORCHEM 820
	PLASTIC NORCHEM 831
	PLASTIC NORCHEM 836
	PLASTIC NORCHEM 8404HJ
	PLASTIC NORCHEM 8410ZR
	PLASTIC NORCHEM 853
	PLASTIC NORCHEM 860
	PLASTIC NORCHEM HND 5903
	PLASTIC NORCHEM NHD 5905
	PLASTIC NORCHEM NHD 6905
	PLASTIC NORCHEM NHD6908
	PLASTIC NORCHEM NPE 130
	PLASTIC NORCHEM NPE 190
	PLASTIC NORCHEM NPE 191
	PLASTIC NORCHEM NPE 195
	PLASTIC NORCHEM NPE 210
	PLASTIC NORCHEM NPE 253
	PLASTIC NORCHEM NPE 265
	PLASTIC NORCHEM NPE 283
	PLASTIC NORCHEM NPE 293
	PLASTIC NORCHEM NPE 3801
	PLASTIC NORCHEM NPE 3855
	PLASTIC NORCHEM NPE 3865
	PLASTIC NORCHEM NPE 510
	PLASTIC NORCHEM NPE 510-3
	PLASTIC NORCHEM NPP 1602WF
	PLASTIC PETOTHENE KR92562
	PLASTIC PETROTHENE FM704
	PLASTIC PETROTHENE FR412
	PLASTIC PETROTHENE FR424
	PLASTIC PETROTHENE FX702
	PLASTIC PETROTHENE FX703
	PLASTIC PETROTHENE FX705
	PLASTIC PETROTHENE KR21017
	PLASTIC PETROTHENE KR901028
	PLASTIC PETROTHENE KR92561
	PLASTIC PETROTHENE LB710
	PLASTIC PETROTHENE LB742
	PLASTIC PETROTHENE LB830
	PLASTIC PETROTHENE LB832
	PLASTIC PETROTHENE LC732
	PLASTIC PETROTHENE LR580
	PLASTIC PETROTHENE LR586
	PLASTIC PETROTHENE LR734
	PLASTIC PETROTHENE LR920
	PLASTIC PETROTHENE NA171
	PLASTIC PETROTHENE NA301
	PLASTIC PETROTHENE NA301-06
	PLASTIC PETROTHENE NA307

MANUFACTURER	DESIGNATION
USI CHEMICALS	PLASTIC PETROTHENE NA309
	PLASTIC PETROTHENE NA310-05
	PLASTIC PETROTHENE NA310-06
	PLASTIC PETROTHENE XL3512
	PLASTIC PETROTHENE XL3700
	PLASTIC PETROTHENE XL5421
	PLASTIC PETROTHENE XL5422
	PLASTIC PETROTHENE XL5423
	PLASTIC PETROTHENE XL5461
	PLASTIC PETROTHENE XL5482
	PLASTIC PETROTHENE XL5483
	PLASTIC PETROTHENE XL5484
	PLASTIC PETROTHENE XL5485
	PLASTIC PETROTHENE XL5486
	PLASTIC PETROTHENE XL5487
	PLASTIC PETROTHENE XL7400
	PLASTIC PETROTHENE XL7403
	PLASTIC PETROTHENE XL7410
	PLASTIC PETROTHENE XL7411
	PLASTIC PETROTHENE YR190505
	PLASTIC PETROTHENE YR19512
	PLASTIC PETROTHENE YR92126
	PLASTIC PETROTHENE YR92273
	PLASTIC PETROTHENE YR92411
	PLASTIC ULTRATHENE UE630 17% VA
	PLASTIC ULTRATHENE UE634 28% VA
	PLASTIC ULTRATHENE UE645 28% VA
	PLASTIC ULTRATHENE UE648 19% VA
	PLASTIC ULTRATHENE UE656-03 12% VA
	PLASTIC ULTRATHENE UE658 12% VA
UTAH FOAM	INSULATION FOAM POLYURETHANE UTAH 320-315
UTICA	CONNECTOR PLIERS UTICA 529
UVEXS CORP	INK MARKING UVEXS 105E BLACK
	RUBBER SILICONE SE4404U WITH SI02 FILLER
VALTEK	GUIDE LINER 1.5 STEM
	GUIDE LINER 2.5 STEM
VAN BUREN INK CO	INK 51022 GREEN/K10 PAPER
VAPOR FAB INC	FARBIC BALLASTIC NYLON COATED WITH NICKEL
VARFLEX CORP	TUBING FIBERGLASS S1600-H
	TUBING VARGLASS 81600H
	TUBING VARGLASS H/HO NON-FRAY
	TUBING VARGLASS VITON 231
	WIRE ELEC VARGLAS SLEEVE
VARIAN ASSOCIATES	SEALANT TORR EPOXY 953-001
VARIOUS	TONOMETER INTRAOCULAR PRESSURE
VARTA BATTERIES	BATTERY NI/CD 5/600KZ 6V
VB 48H-1.0E5-200F	COATING 463-12-8/643-1-1 EPOXY
VB PER MA0105-064	RUBBER SILICONE RTV 560
	RUBBER SILICONE RTV 560 COMPOS
VCM SUBS ALUM .003	COATING EPOXY WHITE TOPCOAT WITH H2 CATALYST
VELCRO CORP	CONFIG NYLON VELCRO/COTTON
	CONFIG NYLON VELCRO/COTTON COF
	COVER DUST FES BETA/VELCRO
	FABRIC COTTON S55 F/P/VELCRO/NOMEX

MSFC-HDBK-527 REV F 9999942 0006968 T

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
VELCRO CORP	FABRIC NOMEX/VELCRO/FC4101
	FASTENER VECRO HI-AIR NYLON HOOK 65 WITH NOMEX GROUND
	FASTENER VELCRO ADHESIVE 45
	FASTENER VELCRO ALL NON MELTING ARAMID LOOP 2000
	FASTENER VELCRO ARAMID HOOK 65 AND LOOP
	FASTENER VELCRO ASTRO HOOK 80 BACKING PS 3072
	FASTENER VELCRO ASTRO HOOK AND LOOP
	FASTENER VELCRO ASTRO LOOP 200 PS 3072
	FASTENER VELCRO ASTRO LOOP 634 WITH BETA GLASS GROUND
	FASTENER VELCRO HAQ 12-2 HOOK AND LOOP BACKING RUBBER SILICONE
	FASTENER VELCRO HI-AIR HOOK 65 WITH PS 0372
	FASTENER VELCRO HI-AIR NOMEX HOOK 65 AND LOOP 2000
	FASTENER VELCRO HI-MEG NYLON LOOP IMPREGNATED WITH SILVER
	FASTENER VELCRO HOOK 80 BACKING 0399
	FASTENER VELCRO HOOK 80 BACKING 1299
	FASTENER VELCRO HOOK 80 BACKING 2699
	FASTENER VELCRO HOOK 80 BACKING 2899
	FASTENER VELCRO HOOK 80 BACKING 9999
	FASTENER VELCRO HOOK 80 LOOP 2000
	FASTENER VELCRO HOOK 80 PS 3072
	FASTENER VELCRO HOOK AND LOOP 100 BACKING 3099AB
	FASTENER VELCRO HOOK AND LOOP 1000 BACKING 0399
	FASTENER VELCRO HOOK SJ3572 AND LOOP SJ3571
	FASTENER VELCRO KNIT NYLON LOOP 3005 BACKING 0699
	FASTENER VELCRO LOOP 2000 BACKING 0100AB
	FASTENER VELCRO LOOP NYLON 80 WITH PS 0172
	FASTENER VELCRO MID-TEMP NYLON HOOK AND LOOP
	FASTENER VELCRO NOMEX HAQ 12-1 HOOK WITH 6-1015 NEOPRENE ADHESIVE
	FASTENER VELCRO NOMEX HAQ 12-1-200 NYLON HOOK
	FASTENER VELCRO NOMEX HAQ 12-2-200 NYLON LOOP
	FASTENER VELCRO NOMEX HI-AIR HAQ 12-1 HOOK AND HAQ 12-2 LOOP
	FASTENER VELCRO NOMEX HI-AIR HAQ 12-2-200-SAI LOOP AND 12-1-200 HOOK
	FASTENER VELCRO NOMEX HI-AIR LOOP 2000 BACKING 0199W
	FASTENER VELCRO NOMEX HI-AIR LOOP 2000 PS 0372
	FASTENER VELCRO NOMEX HOOK 0.75 INCH
VELCRO CORP	FASTENER VELCRO NOMEX HOOK 66 BACKING 0372
	FASTENER VELCRO NOMEX LOOP. 0.75 INCH
	FASTENER VELCRO NOMEX LOOP 1 INCH
	FASTENER VELCRO NOMEX LOOP 1000 BACKING 039
	FASTENER VELCRO NOMEX LOOP 2000 BACKING 0199
	FASTENER VELCRO NOMEX LOOP 2000 BACKING 0399
	FASTENER VELCRO NOMEX LOOP 2000 BACKING 1299
	FASTENER VELCRO NOMEX LOOP 2000 BACKING 2699
	FASTENER VELCRO NOMEX LOOP 2000 BACKING 2899
	FASTENER VELCRO NOMEX LOOP 2000 BACKING 9999
	FASTENER VELCRO NOMEX LOOP 2000 WITH PS 0372 ADHESIVE
	FASTENER VELCRO NOMEX LOOP FR 0327 PRECOAT
	FASTENER VELCRO NYLON 100 BACKING 0172AB
	FASTENER VELCRO NYLON HAQ 12-2-100 LOOP
	FASTENER VELCRO NYLON HOOK 0100
	FASTENER VELCRO NYLON HOOK 2 INCH
	FASTENER VELCRO NYLON HOOK 65
	FASTENER VELCRO NYLON HOOK 65 AND LOOP 1000 BACKING 0199
	FASTENER VELCRO NYLON HOOK 65 BACKING 0199
	FASTENER VELCRO NYLON HOOK 65 BACKING 0399
	FASTENER VELCRO NYLON HOOK 65 BACKING 2699
	FASTENER VELCRO NYLON HOOK 65 BACKING 9999
	FASTENER VELCRO NYLON HOOK 65 BACKING FR8299
	FASTENER VELCRO NYLON HOOK 65 BACKING PS 0100
	FASTENER VELCRO NYLON HOOK 65 BACKING PS 0102
	FASTENER VELCRO NYLON HOOK 65 BACKING PS 0107
	FASTENER VELCRO NYLON HOOK 65 LOOP 1000 BACKING 0399
	FASTENER VELCRO NYLON HOOK 65 LOOP 1000 BACKING 1299
	FASTENER VELCRO NYLON HOOK 65 LOOP 1000 BACKING 2699
	FASTENER VELCRO NYLON HOOK 65 LOOP 1000 BACKING 2899
	FASTENER VELCRO NYLON HOOK 65 LOOP 1000 BACKING 9999
	FASTENER VELCRO NYLON HOOK 65 WITH PS 0104 ADHESIVE
	FASTENER VELCRO NYLON HOOK 65 WITH PS 0140 ADHESIVE
	FASTENER VELCRO NYLON HOOK 65 WITH PS 0172 ADHESIVE

MSFC-HDBK-527 REV F 9999942 0006969 1

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
VELCRO CORP	FASTENER VELCRO NYLON HOOK 66 NON MELTING ARAMID GROUND
	FASTENER VELCRO NYLON HOOK 80
	FASTENER VELCRO NYLON HOOK 80 BACKING 0104
	FASTENER VELCRO NYLON HOOK 80 BACKING 0199W
	FASTENER VELCRO NYLON HOOK 80 WITH PS 0172
	FASTENER VELCRO NYLON HOOK ADHESIVE BACK
	FASTENER VELCRO NYLON HOOK AND LOOP
	FASTENER VELCRO NYLON HOOK AND LOOP 65 BACKING 0399
	FASTENER VELCRO NYLON HOOK AND LOOP 80 BACKING PS 0172
	FASTENER VELCRO NYLON HOOK AND LOOP WITH FR127A ADHESIVE
	FASTENER VELCRO NYLON HOOK HI-MEG
	FASTENER VELCRO NYLON HOOK NOMEX GROUND TAPE WITH FR 0327 PRECOAT
	FASTENER VELCRO NYLON KRAYTON LOOP 1000 PS 0102
	FASTENER VELCRO NYLON LOOP 2000 PS 0104
	FASTENER VELCRO NYLON LOOP 100 BACKING 0199
	FASTENER VELCRO NYLON LOOP 1000
	FASTENER VELCRO NYLON LOOP 1000 BACKING 0199
	FASTENER VELCRO NYLON LOOP 1000 BACKING 0399
	FASTENER VELCRO NYLON LOOP 1000 BACKING 1299
	FASTENER VELCRO NYLON LOOP 1000 BACKING 2699
	FASTENER VELCRO NYLON LOOP 1000 BACKING 2899
	FASTENER VELCRO NYLON LOOP 1000 BACKING PS 0107
	FASTENER VELCRO NYLON LOOP 1000 FR 8299
	FASTENER VELCRO NYLON LOOP 1000 PS 0100
	FASTENER VELCRO NYLON LOOP 1000 PS 0140
	FASTENER VELCRO NYLON LOOP 1000 WITH PS 0104 ADHESIVE
	FASTENER VELCRO NYLON LOOP 1000 WITH PS 0172 ADHESIVE
	FASTENER VELCRO NYLON LOOP 200 BACKING 0199
	FASTENER VELCRO NYLON LOOP 200 PS 3072
	FASTENER VELCRO NYLON LOOP 2000 BACKING 0172
	FASTENER VELCRO NYLON LOOP SJ3418 AND HOOK SJ3419B
	FASTENER VELCRO NYLON LOOP V22-90-W48 BACKING URETHANE FOAM
	FASTENER VELCRO NYLON LOOP WITH FR127 ADHESIVE
VELCRO CORP	FASTENER VELCRO NYLON LOOP WITH PS 0102 ADHESIVE
	FASTENER VELCRO PEEK HOOK AND LOOP
	FASTENER VELCRO POLYESTER HOOK 1 INCH
	FASTENER VELCRO POLYESTER HOOK 80 BACKING 0199
	FASTENER VELCRO POLYESTER HOOK 80 BACKING FR8299
	FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 0199
	FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 0399
	FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 1299
	FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 2699
	FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 2899
	FASTENER VELCRO POLYESTER HOOK 80 LOOP 2000 BACKING 9999
	FASTENER VELCRO POLYESTER HOOK 80 WITH FR PS 8222
	FASTENER VELCRO POLYESTER HOOK 80 WITH Y966 TAPE
	FASTENER VELCRO POLYESTER HOOK H549
	FASTENER VELCRO POLYESTER HOOK H549 FR127A ADHESIVE
	FASTENER VELCRO POLYESTER HOOK H592
	FASTENER VELCRO POLYESTER LOOP 1000 FR PS 8222
	FASTENER VELCRO POLYESTER LOOP 192822/HOOK 192832
	FASTENER VELCRO POLYESTER LOOP 2000
	FASTENER VELCRO POLYESTER LOOP 2000 BACKING 1299
	FASTENER VELCRO POLYESTER LOOP 2000 WITH Y966 TAPE
	FASTENER VELCRO STILAN HOOK BACKING 0399 AND POLYESTER LOOP 2000 BACKING 0399
	FASTENER VELCRO STILAN HOOK BACKING 8299 AND POLYESTER LOOP 2000
	FASTENER VELCRO STILAN HOOK WITH BINDER ADHESIVE 0399
	FASTENER VELCRO STILAN LOOP 0399
	FASTENER VELCRO STILAN POLYESTER HOOK/ ASTRO
	FASTENER VELCRO VELCOIN 1000 PS 0107
	MULTI-LAYERED INSULATION TEDLAR/MYLAR/ 3M838/VELCRO
	MULTI-LAYERED INSULATION TEDLAR/MYLAR/ VELCRO #65
	MULTI-LAYERED INSULATION VELCRO/POLYESTER
	WEBBING NMX/HOOK HAQ-12-1-100
	WEBBING NYLON/VELCRO/NOMEX/METALIZED UTILITY STRAP

MSFC-HDBK-527 REV F 9999942 0006970 8

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
VERNAY LABORATORIES	MOLD COMPOUND URETHANE VL422M2
	RUBBER VITON 1502 H41
	RUBBER VITON VL1502-H141
	RUBBER VITON VL1502H285
	THERMOPLASTIC THERMAL STABILIZ
VERSATEC INC	PAPER ELECTROGRAPHIC 45R11
VIBRA-CHECK	DAMPER VIBRATION VHDS 33 DIDC
VICTOR	REGULATOR OXYGEN
	REGULATOR VICTOR SR250D
VISILOX SYSTEMS	MOLD COMPOUND VISILOX V201 A/B SIL
VITAR	COATING SILICONE PV100 WHITE
VIVIAN WOODWARD	EYE SHADOW #35-4.023-4091
VOLTAX CO	COATING E2359A/B EPOXY
VOLTEK	INSULATION FOAM MINICELL L200 FR
	INSULATION FOAM MINICELL L200 POLYETHYLN
	INSULATION FOAM MINICELL L200/FREKOTE COATED
VOUGHT	LAMIN EPOXY/PC12-007M COATED
W H BRADY	DECALS AF-1-33/TAPE B-184
	LABELS BRADY 684 TEFLON
	LABELS BRADY XB652 HIGH TEMPERATURE
	TAPE J677 VINYL CLOTH WITH SILICONE ADHESIVE
W L GORE	ADHESIVE POLYAMIDE SL6
	CABLE COAX RG179 PTFE CORE FEP JACKET SILVER COATED COPPER
	CABLE COAX RG6178 PTFE CORE FEP JACKET SILVER COATED COPPER
	CABLE ELEC URETHANE J210/BLK
	ETCHANT
	FABRIC DELNET R0709 POLYPROPYL
	FABRIC GORTEX 1/8 TFE FLUOROCARBON JOINT SEALANT
	FABRIC GORTEX 1/8 TFE FLUOROCARBON PIPE SEALANT ADHES
	FABRIC GORTEX P/N L11517
	FABRIC NOMEX-KEVLAR/TFE/GORTEX
	FABRIC NOMEX/TFE COATED
	FILM GORETEX 1/4" TFE PIPE SEALANT WITH ADHESIVE
	FILM GORETEX 1/4" TFE PIPE SEALANT/ NONADHESIVE
	FILM GORTEX LAMIN WITH FABRIC NOMEX
	FILM TEFLON GORTEX
	FILTER MEDIA TFE GORE-TEX
	TAPE PTFE (EXPANDED)
	TAPE PTFE EXPANDED/NON ADHESIVE
	TAPE TEFLON
	TETRA-ETCH FLUOROCARBON
	THREAD GORE-TEX S012T3 PTFE
	WIRE ELEC E050A040
	WIRE GSC 1620
W R GRACE	INSULATION FOAM HYPOL 4 URETHANE
	INSULATION FOAM HYPOL FHP3000 POLYURETHANE
W S LIBBEY	FABRIC NOMEX FELT X-547
W S SHAMBAN	TRUCITE A BLUE
W T BEAN	ADHESIVE EPOXY RTC
	COATING GAGEKOTE 5
	COATING GAGEKOTE 8
	SEALANT GAGEKOTE 3 SILICONE
W18161	RUBBER SILICONE HT 2-80 SHOCK ISOLATOR
WAHL INSTRUMENT	ADHESIVE SILICONE DA4
WAKEFIELD	ADHESIVE DELTABOND 152 WITH A4
	ADHESIVE DELTABOND 152 WITH B4
	ADHESIVE DELTABOND 152 WITH C4
	ADHESIVE DELTABOND 152 WITH D4
	ADHESIVE DELTABOND 154 WITH A4
	ADHESIVE DELTABOND 154 WITH B4
	ADHESIVE DELTABOND 154 WITH C4
	ADHESIVE DELTABOND 154 WITH D4
	ADHESIVE DELTABOND 155
	ADHESIVE DELTACAST 153 WITH A4
	ADHESIVE DELTACAST 153 WITH B4
	ADHESIVE DELTACAST 153 WITH C4
	ADHESIVE DELTACAST 153 WITH D4
	COMPOUND HEAT SINK THERMAL 120
WALTER SARSTEDT	ACRYLIC CUVETTE 749 (BCS)
WALTERS ENG PROD	HEATER BELT AV14493
WARNER LAMBERT CO	BLADES RAZOR SCHICK SUPER II
WARREN WIRE	LACING TAPE T3333
WASHINGTON PENN PLASTICS	PLASTIC ABSG1FG2
	PLASTIC PE25
	PLASTIC PE2FR
	PLASTIC PE3CC3
	PLASTIC PE47MF1
	PLASTIC PP-C2TF4
	PLASTIC PP-C3CC4
	PLASTIC PP-C3TF2
	PLASTIC PP-C4IM-V
	PLASTIC PP-C5CC2
	PLASTIC PP-C6CC4
	PLASTIC PP-H1CC1
	PLASTIC PP-H2CC2
	PLASTIC PP-H2LTF4
	PLASTIC PP-H2MFQ3
	PLASTIC PP-H2MFQ4
	PLASTIC PP-H2MFS3
	PLASTIC PP-H2MFS4
	PLASTIC PP-H2TF2
	PLASTIC PP-H3MF2
	PLASTIC PP-H3MFO5
	PLASTIC PP-H4CG4
	PLASTIC PP-H4TF3
	PLASTIC PP-H6CC4
	PLASTIC PP-H7CC4
	PLASTIC PP-HFG1
	PLASTIC PP-HFG2
	PLASTIC PP-HFG3
	PLASTIC PP-HFGC2
	PLASTIC PP-HFGC3

MSFC-HDBK-527 REV F 9999942 0006971 T

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
WASHINGTON PENN PLASTICS	PLASTIC PP-HIFR
	PLASTIC PP-TFFR2
	PLASTIC PP1MT3
	PLASTIC VB511
WATANABE	RECORDER STRIP CHART
WATLOW	HEATER WATLOW 02205580
WEIDMULLER	CONNECTOR ELECT GLASS/PHENOLIC
WELLINGTON PURITAN	CORD DACRON BRAIDED TROLL 70LB
	CORD NYLON G1008 1/8 DIA
	CORD POLYESTER
WELLMAN INC	PLASTIC WELLAMID 210N
	PLASTIC WELLAMID 21L-N
	PLASTIC WELLAMID 21LH-N
	PLASTIC WELLAMID 21LN2-NNT
	PLASTIC WELLAMID 21U-NBK1
	PLASTIC WELLAMID 220N
	PLASTIC WELLAMID 22L-N
	PLASTIC WELLAMID 22LH-N
	PLASTIC WELLAMID 22LH13XE-N
	PLASTIC WELLAMID 22LH14XE-N
	PLASTIC WELLAMID 22LH15XE-N
	PLASTIC WELLAMID 22LN2-N
	PLASTIC WELLAMID 33LH16XE-N
	PLASTIC WELLAMID 420N
	PLASTIC WELLAMID 420XE-N
	PLASTIC WELLAMID 42HI11-XE-N
	PLASTIC WELLAMID 42L-N
	PLASTIC WELLAMID 42L-XE-N
	PLASTIC WELLAMID 42LH-N
	PLASTIC WELLAMID 42LH-XE-N
	PLASTIC WELLAMID 42LN-2-N
	PLASTIC WELLAMID 42LN-2-XE-N
	PLASTIC WELLAMID FR22F-N
	PLASTIC WELLAMID FR64-NRD
	PLASTIC WELLAMID FRGF25-66-N
	PLASTIC WELLAMID FRGS25-66-N
	PLASTIC WELLAMID GF13-60-42LH-N
	PLASTIC WELLAMID GF13-66 X3-N
	PLASTIC WELLAMID GF13-66-22LH-N
	PLASTIC WELLAMID GF30-60 42LH-N
	PLASTIC WELLAMID GF30-60 XE-N
	PLASTIC WELLAMID GF33-66 22LH-N
	PLASTIC WELLAMID GF33-66 XE-N
	PLASTIC WELLAMID GF33-66 XE-N1
	PLASTIC WELLAMID GFT13-66 XE-N
	PLASTIC WELLAMID GR43-66 XE-N1
	PLASTIC WELLAMID GS25-66 22L-N
	PLASTIC WELLAMID GS25-66 LH-N
	PLASTIC WELLAMID GS40-60 22L-N
	PLASTIC WELLAMID GS40-60 42L-N
	PLASTIC WELLAMID GS40-60 42LH-N
	PLASTIC WELLAMID GSF25/15-66 22L-N
	PLASTIC WELLAMID MR259 22LH-N
	PLASTIC WELLAMID MR409 22H-N
	PLASTIC WELLAMID MR410 22H-N

MANUFACTURER	DESIGNATION
WELLMAN INC	PLASTIC WELLAMID MRGF25/15 22H-N
	PLASTIC WELLAMID MRGF25/15 42H-N
	PLASTIC WELLAMID MRGF30/10 42H-N
	PLASTICS WELLITE 9000GP
	PLASTICS WELLITE 9320GR
	PLASTICS WELLITE 9330GR
	PLASTICS WELLITE 9730GRVO
	PLASTICS WELLPET FG1020
	PLASTICS WELLPET FRGF2030
	PLASTICS WELLPET GF1030
	PLASTICS WELLPET GF1045
WESFIELD CHEMICAL	COATING LACQUER NO.2 OSC877
WEST AMERICAN RUBBER	RUBBER NITRILE (NRB)
WESTERN ELECTRIC	CLIPS CORD B2
WESTERN FILAMENT	CORD KEVLAR 275KOZ3/300 POLYU
	CORD KEVLAR POLYURETHANE COATED
	CORD KRT-300 ARAMID
	LACING TAPE FIBERGLAS 50LOF13X
	LACING TAPE NOMEX
	LACING TAPE NOMEX 950HOT16
	LACING TAPE NOMEX/P/N 950HOT16
	TAPE KEVLAR POLYURETHANE COATED
WESTERN PIECE DYERS	FABRIC 100% COTTON FR 7 OZ BLUE
	FABRIC FR COTTON 7 OZ/SQ YD
WESTERN SINCLAIR	TAPE MYLAR/ACRYLIC PS ADHESIVE
WESTEX INC	FABRIC COTTON FR7A FIRE STOP
	FABRIC COTTON S55 F/P/VELCRO/NOMEX
	FABRIC COTTON S55 F/PNH3 D/F
	FABRIC COTTON S65 F/PNH3 D/F
WESTINGHOUSE	ADHESIVE EPOXY B101
	GLASS FLUORESCENT TUBE LAMP
	LAMIN COTTON/PHENOLIC
	LAMIN EPOXY/GLASS
	LAMIN EPOXY/GLASS 7070664
	LAMIN EPOXY/GLASS NEMA G11
	LAMIN G1065M-28-S12 WITH COPPER
	LAMIN URALANE 5570 COATED WITH FC721
	RUBBER SPONGE NEOPRENE
	VARNISH DORYL DIPHENYL OXIDE
WESTLAKE PLASTICS CO	FILM KYNAR NATURAL
	FILM KYNAR NATURAL TOX RATE STUDY
	KYNAR 460
	KYNAR 740
	KYNAR PLASTIC FLUORIDE
	PLASTIC LEXAN ZELUX M GLASS FILLED
	PLASTIC POLYMETHYLPENTENE DX 845
	PLASTIC POLYSULFONE P1700
	PLASTIC THERMALUX UDEL POLYSULFONE
	PLASTIC VICTREX PEEK
	PLASTIC WESTLAKE CELCON/25PCT GLASS
	PLASTIC WESTLAKE CELCON/UNFILLED
	PLASTIC WESTLAKE ETHYLUX
	PLASTIC WESTLAKE LENNITE
	PLASTIC WESTLAKE LENNITE UHMW
	PLASTIC WESTLAKE LENNITE XL

MSFC-HDBK-527 REV F 9999942 0006972 1

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
WESTLAKE PLASTICS CO	PLASTIC WESTLAKE NORYL EN-185
	PLASTIC WESTLAKE NORYL SE-1-GFN3
	PLASTIC WESTLAKE POLYMETHYLPENTENE
	PLASTIC WESTLAKE POLYSTYRENE
	PLASTIC WESTLAKE PROPYLUX
	PLASTIC WESTLAKE STYROLUX
	PLASTIC WESTLAKE VICTREX
	PLASTIC WESTLAKE VICTREX 4101GL30 (30 PCT REINFORCED)
	PLASTIC WESTLAKE ZELUX
	PLASTIC WESTLAKE ZELUX 10 PCT GLASS REINFORCED
	PLASTIC WESTLAKE ZELUX 20 PCT GLASS REINFORCED
	PLASTIC WESTLAKE ZELUX 40 PCT GLASS REINFORCED
	PLASTIC WESTLAKE ZELUX W
	PLASTIC ZELUX M131
	ULTRA ETHYLUX POLYETHYLENE
WESTON INSTRUMENTS	PWB COPPER CLAD GLASS FABRIC EPOXY RESIN FR4 COATED WITH HUMISEAL/INDICATOR MODEL 2495 ATTACHED TO BOARD
WESTWOOD	CREAM HAND/KERI
WHATMAN	PAPER FILTER WHATMAN #1
	PAPER FILTER WHATMAN #42
WHITFORD CORP	COATING XYLAN 1010 BLACK
	ROD TEFLON/25% GLASS
	TEFLON TFE/25% GLASS
WIEDERHOLD	COATING CHEMGLAZE II A471
WILLIAM F NYE INC	COATING NYEBAR TYPE CT
	FILM NYEBAR CT FLUOROCARBON BARRIER
	LUBE GREASE D840924A T1
	LUBE GREASE NYE 899
	LUBE GREASE RHEOLUBE 738
	LUBE OIL CORR INHIBIT X90315
WILLIAM T. BEAN MICRO ENGINEER	ADHESIVE BR610
	ADHESIVE CA2005L
	ADHESIVE HIGH STRENGTH RTC EPOXY
	ADHESIVE RTC EPOXY
WILMINGTON CHEM CO	COATING HELASTIC 2010
	COATING HELASTIC 23GD102
	COATING HELASTIC 25GD102
	COATING HELASTIC X768 POLYURETHANE
	COMPOUND EPOXY 8013R/8012H
	INK KP402 URETHANE WHITE T102
WILSHIRE FOAM	INSULATION FOAM PYRELL WFP1406 CHARCOA
	INSULATION URETHANE UNIFOAM S82N
WILSON FIBERFIL	NYLAFIL G-12/40
	PLASTIC ABSAFIL G1200/10
	PLASTIC ABSAFIL J1200/20
	PLASTIC ABSAFIL J1200/30
	PLASTIC ACRYAFIL G40/20
	PLASTIC ACRYAFIL G40/20/V0
	PLASTIC ACRYAFIL G40/30/V0
	PLASTIC ACRYAFIL G40/35

MANUFACTURER	DESIGNATION
WILSON FIBERFIL	PLASTIC ELECTRAFIL 50EC-1
	PLASTIC ELECTRAFIL 50EC-2
	PLASTIC ELECTRAFIL 70EC-1
	PLASTIC ELECTRAFIL 75EC1
	PLASTIC ELECTRAFIL 75EC3
	PLASTIC ELECTRAFIL ABS1200 AF40FR
	PLASTIC ELECTRAFIL G1/SS/5
	PLASTIC ELECTRAFIL G100/SS/10
	PLASTIC ELECTRAFIL G1700/SS/3/BK5658
	PLASTIC ELECTRAFIL G3/10/CF/25
	PLASTIC ELECTRAFIL G50/30/CF/10
	PLASTIC ELECTRAFIL G50/CF/20
	PLASTIC ELECTRAFIL G50/CF/40
	PLASTIC ELECTRAFIL G50/CF/5/SS/5
	PLASTIC ELECTRAFIL G50/SS/10
	PLASTIC ELECTRAFIL G50/SS/5/FR
	PLASTIC ELECTRAFIL J1/15/CP/30
	PLASTIC ELECTRAFIL J1/CF/10
	PLASTIC ELECTRAFIL J1/CF/15/TF/20
	PLASTIC ELECTRAFIL J1/CF/20
	PLASTIC ELECTRAFIL J1/CF/30
	PLASTIC ELECTRAFIL J1/CF/30/TF/13/SI/2
	PLASTIC ELECTRAFIL J1/CF/30/TF/15
	PLASTIC ELECTRAFIL J1/CF/40
	PLASTIC ELECTRAFIL J1/CF/40/VO/OD5208
	PLASTIC ELECTRAFIL J1/CF/50
	PLASTIC ELECTRAFIL J1/CN/15
	PLASTIC ELECTRAFIL J1/CN/40
	PLASTIC ELECTRAFIL J1/CP/20
	PLASTIC ELECTRAFIL J1/CP/30
	PLASTIC ELECTRAFIL J1/CP/40
	PLASTIC ELECTRAFIL J100/CF/30
	PLASTIC ELECTRAFIL J105/CF/30
	PLASTIC ELECTRAFIL J1100/CF/30
	PLASTIC ELECTRAFIL J1105/CF/30
	PLASTIC ELECTRAFIL J1106/CF/30
	PLASTIC ELECTRAFIL J1200/CF/10
	PLASTIC ELECTRAFIL J1200/CF/20
	PLASTIC ELECTRAFIL J1200/SS/7/BK2089
	PLASTIC ELECTRAFIL J1300/10/CF/5/SS/5
	PLASTIC ELECTRAFIL J1300/CF/15/CP/15
	PLASTIC ELECTRAFIL J1300/CF/20
	PLASTIC ELECTRAFIL J1300/CF/20/MS/10/TF/15
	PLASTIC ELECTRAFIL J1300/CF/30
	PLASTIC ELECTRAFIL J1300/CF/30/TF/15
	PLASTIC ELECTRAFIL J1300/CF/40
	PLASTIC ELECTRAFIL J1300/CF/50/HM
	PLASTIC ELECTRAFIL J1300/CN/15
	PLASTIC ELECTRAFIL J1300/CN/40
	PLASTIC ELECTRAFIL J1400/CF/20
	PLASTIC ELECTRAFIL J1405/CF/30
	PLASTIC ELECTRAFIL J1500/CF/20
	PLASTIC ELECTRAFIL J1500/CF/30
	PLASTIC ELECTRAFIL J1700/CF/10
	PLASTIC ELECTRAFIL J1700/CF/20

MSFC-HDBK-527 REV F 9999942 0006973 3

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
WILSON FIBERFIL	PLASTIC ELECTRAFIL J1800/CF/30
	PLASTIC ELECTRAFIL J1850/CF/30
	PLASTIC ELECTRAFIL J3/CF/30
	PLASTIC ELECTRAFIL J3/CF/40
	PLASTIC ELECTRAFIL J3/CF/50
	PLASTIC ELECTRAFIL J30/CF/20
	PLASTIC ELECTRAFIL J4/CF/30/TF/10
	PLASTIC ELECTRAFIL J4/CF/40
	PLASTIC ELECTRAFIL J50/CF/10
	PLASTIC ELECTRAFIL J50/CF/10/TF/15/FR
	PLASTIC ELECTRAFIL J50/CF/20
	PLASTIC ELECTRAFIL J50/CF/20/TF/15
	PLASTIC ELECTRAFIL J50/CF/30
	PLASTIC ELECTRAFIL J50/CF/40
	PLASTIC ELECTRAFIL J50/CP/25/FR
	PLASTIC ELECTRAFIL J60/CF/30
	PLASTIC ELECTRAFIL J60/CP/40
	PLASTIC ELECTRAFIL J8/15/CF/15
	PLASTIC ELECTRAFIL J80/CF/10/TF/10
	PLASTIC ELECTRAFIL JI/CF/15
	PLASTIC ELECTRAFIL SMA38/AF/40
	PLASTIC ETHOFIL G90/20
	PLASTIC ETHOFIL G90/30
	PLASTIC ETHOFIL J90/20
	PLASTIC ETHOFIL J90/30
	PLASTIC FIBERFIL G2/10
	PLASTIC FIBERFIL G2/20
	PLASTIC FIBERFIL G2/30
	PLASTIC FIBERFIL G2/40
	PLASTIC FIBERFIL J1105/30
	PLASTIC FIBERFIL J1106/20
	PLASTIC FIBERFIL J1106/30
	PLASTIC FIBERFIL J11106/40
	PLASTIC FIBERFIL J1300/25/MF/40
	PLASTIC FIBERFIL J1700/20
	PLASTIC FIBERFIL J1700/30
	PLASTIC FIBERFIL J1700/40
	PLASTIC FIBERFIL J2/10
	PLASTIC FIBERFIL J2/20
	PLASTIC FIBERFIL J2/30
	PLASTIC FIBERFIL J2/40
	PLASTIC FORMALDAFIL AC80/TF/10
	PLASTIC FORMALDAFIL AC80/TF/15
	PLASTIC FORMALDAFIL AC80/TF/20
	PLASTIC FORMALDAFIL J80/10
	PLASTIC FORMALDAFIL J80/20
	PLASTIC FORMALDAFIL J80/20/TF/15
	PLASTIC FORMALDAFIL J80/30
	PLASTIC FORMALDAFIL J80/30/TF/15
	PLASTIC FORMALDAFIL J82/10
	PLASTIC FORMALDAFIL J82/25
	PLASTIC FORMALDAFIL J82/40
	PLASTIC METHAFIL J-98/10
	PLASTIC METHAFIL J-98/20
	PLASTIC METHAFIL J-98/30

MANUFACTURER	DESIGNATION
WILSON FIBERFIL	PLASTIC METHAFIL J-98/40
	PLASTIC NYAFIL 6
	PLASTIC NYAFIL 6/12
	PLASTIC NYAFIL G-1/10/CF/30
	PLASTIC NYAFIL G-1/30 AND G-1/30/HS
	PLASTIC NYAFIL G-1/30/MS/5
	PLASTIC NYAFIL G-1/30/SI/2
	PLASTIC NYAFIL G-1/30/TF/15
	PLASTIC NYAFIL G-1/40
	PLASTIC NYAFIL G-1/40/MS/5
	PLASTIC NYAFIL G-1/CF/30
	PLASTIC NYAFIL G-3/30
	PLASTIC NYAFIL G-3/40
	PLASTIC NYAFIL G-4/35
	PLASTIC NYAFIL G-4/45
	PLASTIC NYAFIL G-8/40
	PLASTIC NYAFIL J-1/15/MF/25
	PLASTIC NYAFIL J-1/20/FR
	PLASTIC NYAFIL J-1/30 AND J-1/30/HS
	PLASTIC NYAFIL J-1/30/MS/15
	PLASTIC NYAFIL J-1/30/MS/5
	PLASTIC NYAFIL J-1/30/SI/3
	PLASTIC NYAFIL J-1/30/TF/15
	PLASTIC NYAFIL J-1/33 AND J-1/33/HS
	PLASTIC NYAFIL J-1/33/TF/13/SI/2
	PLASTIC NYAFIL J-1/40/MU/20
	PLASTIC NYAFIL J-1/43
	PLASTIC NYAFIL J-1/CF/30
	PLASTIC NYAFIL J-1/CF/30/TF/13/SI/2
	PLASTIC NYAFIL J-1/CP/30
	PLASTIC NYAFIL J-17/20/VO
	PLASTIC NYAFIL J-17/20/VO/TF/15
	PLASTIC NYAFIL J-17/30/VO
	PLASTIC NYAFIL J-2/30/VO
	PLASTIC NYAFIL J-29/33
	PLASTIC NYAFIL J-29/8/MB/22
	PLASTIC NYAFIL J-3/15/MF/25
	PLASTIC NYAFIL J-3/30
	PLASTIC NYAFIL J-3/30/VO
	PLASTIC NYAFIL J-3/40
	PLASTIC NYAFIL J-4/30/TF/15
	PLASTIC NYAFIL J-4/30/VO
	PLASTIC NYAFIL J-4/35
	PLASTIC NYAFIL J-4/45
	PLASTIC NYAFIL J-4/CF/40
	PLASTIC NYAFIL J-6/25
	PLASTIC NYAFIL J-6/50
	PLASTIC NYAFIL J-7/13
	PLASTIC NYAFIL J-7/33
	PLASTIC NYAFIL J-7/43
	PLASTIC NYAFIL J-70/30
	PLASTIC NYAFIL J-71/20
	PLASTIC NYAFIL J-8/13
	PLASTIC NYAFIL J-8/30
	PLASTIC NYAFIL J-8/33

MSFC-HDBK-527 REV F 9999942 0006974 5

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
WILSON FIBERFIL	PLASTIC NYAFIL J-8/43
	PLASTIC NYAFIL MG-1/40
	PLASTIC NYAFIL NY-1/EC
	PLASTIC NYAFIL NY-1/MS/5
	PLASTIC NYAFIL NY-1/SI/5
	PLASTIC NYAFIL NY-1/TC/30
	PLASTIC NYAFIL NY-1/TF/15
	PLASTIC NYAFIL NY-16/MF/40
	PLASTIC NYAFIL NY-17/MF/40
	PLASTIC NYAFIL NY-3/EC
	PLASTIC NYAFIL NY-3/TC/40
	PLASTIC NYAFIL NY-7
	PLASTIC NYAFIL NY-8
	PLASTIC NYAFIL NY-8/MF/36
	PLASTIC NYAFIL NY3/20/75
	PLASTIC NYAFIL TYPE 6/10 NYLON UNREINFORCED
	PLASTIC NYAFIL UNREINFORCED 612
	PLASTIC NYAFIL UNREINFORCED SUPER TOUGH TYPE 12
	PLASTIC NYAFIL UNREINFORCED TYPE 12
	PLASTIC NYAFIL UNREINFORCED TYPE 6
	PLASTIC NYAFIL UNREINFORCED TYPE 66
	PLASTIC NYAFIL VO NY-7/VO
	PLASTIC NYAFIL XYLON FR
	PLASTIC NYAFIL XYLON/VO
	PLASTIC NYLAFIL G-3/30 MS/5
	PLASTIC NYLAFIL G-3/40 MS/5
	PLASTIC NYLAFIL J-1/20
	PLASTIC NYLAFIL J-3/20
	PLASTIC NYLAFIL POLYCARBAFIL G-50/20
	PLASTIC PLASTALLOY J-1505/10
	PLASTIC PLASTALLOY J-1505/30
	PLASTIC PLASTALLOY J-1505/40
	PLASTIC POLYCARBAFIL F-50/20/FR
	PLASTIC POLYCARBAFIL G-50/20/FR
	PLASTIC POLYCARBAFIL G-50/30
	PLASTIC POLYCARBAFIL J-5/30/FR
	PLASTIC POLYCARBAFIL J-50/20/FR
	PLASTIC POLYCARBAFIL J-50/40
	PLASTIC POLYCARBAFIL J-50/M/5/CE/10
	PLASTIC POLYCARBAFIL J-54/10
	PLASTIC POLYCARBAFIL/FOAM F-50/10
	PLASTIC POLYCARBAFIL/FOAM F-50/20
	PLASTIC POLYCARBAFIL/FOAM F-50/20 LONG GLASS
	PLASTIC POLYCARBAFIL/FOAM F-50/30
	PLASTIC POLYCARBAFIL/FOAM F-50/40
	PLASTIC PROFIL G-60/20
	PLASTIC PROFIL G-60/30
	PLASTIC PROFIL J-60/10/E3
	PLASTIC PROFIL J-60/10/E4
	PLASTIC PROFIL J-60/20
	PLASTIC PROFIL J-60/20/E
	PLASTIC PROFIL J-60/20/E3
WILSON FIBERFIL	PLASTIC PROFIL J-60/20/E4
	PLASTIC PROFIL J-60/30
	PLASTIC PROFIL J-60/30/E
	PLASTIC PROFIL J-60/30/ER
	PLASTIC PROFIL J-60/30/FR
	PLASTIC PROFIL J-60/40
	PLASTIC PROFIL J-60/40/E
	PLASTIC PROFIL J-60/40/E3
	PLASTIC PROFIL J-60/40/ER
	PLASTIC PROFIL J-61/10/NAT
	PLASTIC PROFIL J-61/20/NAT
	PLASTIC PROFIL J-61/30/NAT
	PLASTIC PROFIL J-61/40/NAT
	PLASTIC PROFIL J-62/10/E4
	PLASTIC PROFIL J-62/20/E4
	PLASTIC PROFIL J-62/30/E4
	PLASTIC PROFIL J-62/40/E4
	PLASTIC PROFIL PF-6000
	PLASTIC PROFIL PF-6000/EC
	PLASTIC PROFIL PF-6001
	PLASTIC PROFIL PF-6010
	PLASTIC PROFIL PF-6012
	PLASTIC PROFIL PF-6013
	PLASTIC PROFIL PF6020
	PLASTIC PROFIL PF6022
	PLASTIC PROFIL PF6023
	PLASTIC PROFIL PF6024
	PLASTIC PROFIL PP-60 FR
	PLASTIC PROFIL PP-60/CC/20
	PLASTIC PROFIL PP-60/CC/40
	PLASTIC PROFIL PP-60/TC/20
	PLASTIC PROFIL PP-60/TC/40
	PLASTIC PROFIL PP-61/CC/20
	PLASTIC PROFIL PP-61/CC/40
	PLASTIC PROFIL PP-61/TC/20
	PLASTIC PROFIL PP-61/TC/40
	PLASTIC PROFIL PP-62/MI/40
	PLASTIC PROFIL PP-62/TC/20
	PLASTIC PROFIL PP-62/TC/40
	PLASTIC PROFIL/FOAM F-60/20
	PLASTIC STYRAFIL G-30/20
	PLASTIC STYRAFIL G-30/30
	PLASTIC STYRAFIL G-35/35
	PLASTIC STYRAFIL J-30/20
	PLASTIC STYRAFIL J-30/30
	PLASTIC STYRAFIL J-39/10
	PLASTIC STYRAFIL J-39/10/E
	PLASTIC STYRAFIL J-39/20
	PLASTIC STYRAFIL J-39/20/D
	PLASTIC STYRAFIL J-39/20/E
	PLASTIC STYRAFIL J-39/30
	PLASTIC STYRAFIL J-39/30/E
	PLASTIC STYRAFIL J-39/40
	PLASTIC STYRAFIL J-39/40/E
	PLASTIC SULFIL G-1500/10

MSFC-HDBK-527 REV F 9999942 0006975 7

Information Handling Services, 2000

MANUFACTURER	DESIGNATION
WILSON FIBERFIL	PLASTIC SULFIL G-1500/20
	PLASTIC SULFIL J-1100/20
	PLASTIC SULFIL J-1100/30
	PLASTIC SULFIL J-1100/40
	PLASTIC SULFIL J-1105/30
	PLASTIC SULFIL J-1300/10
	PLASTIC SULFIL J-1300/20
	PLASTIC SULFIL J-1300/30
	PLASTIC SULFIL J-1300/30/TF/15
	PLASTIC SULFIL J-1300/40
	PLASTIC SULFIL J-1500/10
	PLASTIC SULFIL J-1500/20
	PLASTIC SULFIL J-1500/20/TF/15
	PLASTIC SULFIL J-1500/30
	PLASTIC SULFIL J-1500/40
	PLASTIC SULFIL J-1505/20
	PLASTIC TETRAFIL J-1800/30
	PLASTIC TETRAFIL J-1800/30/VO
	PLASTIC TETRAFIL J-1800/45
	PLASTIC TETRAFIL J-1800/55
	PLASTIC TETRAFIL J-1850/15
	PLASTIC TETRAFIL J-1850/30/VO
	PLASTIC TETRAFIL J1875/30/VO
	PLASTIC XYLON/VO NYLON UNREINFORCED
WILSON SALES CO	PLASTIC ELECTROSAFE
WINTON PRODUCTS	LEAK DETECTOR SHERLOCK 5 SEC
WITCO	COATING IRIDITE 7 INORGANIC
	INSULATION FOAM POLYURETHANE ISOFOAM SS0658
	INSULATION FOAM POLYURETHANE ISOFOAM SS0991
	INSULATION FOAM POLYURETHANE WITH COATING URETHANE
WOLFF ENGINEERING	SAPPHIRE
WOODBRIDGE FOAM	INSULATION FOAM GRADE 1830
WORCESTER BRAIDING	CORD ELASTIC NOMEX COVERED
WRIGHT & CO	TUBING POLYIMIDE ARAMID
WSTF	IGNITION HAZARD PROOFING OF VLS ENVIRONMENTAL SAMPLERS
WYOMISSING CORP	TAPE ELASTIC 14738P/B8209W
X1-1401/X1-1077	ADHESIVE URALANE 5738 A/B POLYURETHANE
XCA/PR1-XAA/PR2-XFA	COATING CHEMGLAZE Z651 POLYURETHANE 9924
XEA/PR1-XAA/PR2-XFA	COATING CHEMGLAZE Z752 POLYURETHANE 9924
XEROX	INK DRY 9200/JCP E20 PAPER
	INK DRY 9200/JCP K10 PAPER
	PAPER XEROX 4200
	TONER XEROX 6500
YALE CORDAGE INC	CORD YALE 375 QUAD DACRON/KEV
YASUTOMO & CO	MARKER METALLIC NIJI GOLD
	MARKER METALLIC NIJI GREEN
	MARKER METALLIC NIJI SILVER
	MARKER METALLIC NIJI WHITE
YDE BOARD	LAMIN DC6-1104 AND REFSET COATED
YKK ZIPPER CO	ZIPPER NYLON CHAIN 10VF
	ZIPPER POLYESTER/DELRIN VFC 56
YKK ZIPPER CO	ZIPPER YGC 459
YYB SHAMB & CO	ETCHANT-BONDAIV S16943
ZEISS	RUBBER SILICONE O-RINGS
ZEUS INDUSTRIAL	TUBING PTFE SHRINKABLE
ZIPPERTUBING	FABRIC SILICONE/GLASS WITH ZIPPER
	WIRE ELEC RAYCHEM 44 WITH ATLAS TUBE
	WIRE ELEC RAYCHEM 44 WITH FEP TUBING
ZIRCONIUM CORP	INSULATION GLASS WOOL F100

MSFC-HDBK-527 REV F 9999942 0006976 9

Information Handling Services, 2000

TABLE 3

STANDARD/COMMERCIAL PARTS REPORT

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
02-0104-0775-31	10445	PLATING TIN	
	10678	WIRE - COPPER CLAD STEEL	
04-0102	06157	GASKET RFI SILICONE/AL	
05-0860-2880-04	10445	PLATING TIN	
	10678	WIRE - COPPER CLAD STEEL	
1-21221K0328	10217	AL 1100	PLATE , BASE
1-21223K0329	50055	AL 2024/T62	BASE PLATE
	00666	CTNG CONVERSION CHROMATE	
	05015	PRIMER SUPER KDRDPON 515-700	
1-21225K0330	10334	CRES 302	SOCKET,FASTENER
1-60001K8367-105	05143	RUBBER SILICONE	WASHER
100-006-715-XXX	10268	CRES 300 SERIES FASTENER MATL	
	05073	VELCRO MID-TEMP NOMEX/METAL	
100-008-306-XXX	10268	CRES 300 SERIES FASTENER MATL	
100-046-306-XXX	10268	CRES 300 SERIES FASTENER MATL	
1000-0040	05364	RUBBER DC 675 SIL.	SEAL RING
1000-0040-12	61735	RUBBER SILASTIC 675	SEAL (RING)
1000-R	30999	AL ALLOY (NOT OTHERWISE SPECIF	RIVET
1005-0011	10268	CRES 300 SERIES	SCREW CAP BUTTON HEX
1005-0013	10268	CRES 300 SERIES	SCREW, MACH. FL.HD.82
1005-0015	10268	CRES 300 SERIES	SCREW,MACH. FILLISTER
1005-0017	10268	CRES 300 SERIES	SET SCR. HEX. SOC.OVAL
1005-0018	10268	CRES 300 SERIES	SCREW,CAP. SOC.HD. HEX
1005-0019-	10268	CRES 300 SERIES	SCREW
1005-0020	10268	CRES 300 SERIES	SCREW CAPTIVE
1005-0021	10268	CRES 300 SERIES	SCREW 100 FLAT HEAD
1005-0022	10268	CRES 300 SERIES	SCREW
100F391781	50835	AL 2114	WASHER
	00666	CTNG. CONVERSION CHROMATE	
100F394649	50835	AL 2114	WASHER
	00666	CTNG. CONVERSION CHROMATE	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
100F394744	62633	CTNG. CHEMGLAZE II A871	BOLT
	10069	TI 6AL 4V	
100F394745	62634	CHEMGLAZE II A371 CTNG.	BOLT
	10069	TI 6AL 4V	
100F394746	06236	CTNG. CHEMGLAZE II A276	BOLT
	10069	TI 6AL 4V	
100F394747	62630	CTNG. CHEMGLAZE II A671	BOLT
	10069	TI 6AL 4V	
100F394748	62631	CTNG. CHEMGLAZE II A571	BOLT
	10069	TI 6AL 4V	
100F394749	62632	CTNG. CHEMGLAZE II A971	BOLT
	10069	TI 6AL 4V	
1025-0001	10271	BE-CU HT/AT BAR ROD WIRE FRG	
	10321	BRASS, ALL FORM	
	10328	PLATING GOLD	
	10039	PLATING SILVER	
	05149	RUBBER 960-C-1778 SIL-GRADE 60	
	00016	TEFLON TFE	
1030-0012	05130	KEL-F-81	LOCK PLUG
1037-1-05	10321	BRASS	SOLDER TERMINAL
	10311	CU PLATE	
1055-0010	05128	BRAYCO 3L-38RP	GREASE
10622	10431	CRES 300 SERIES	WASHER-FLAT
10E1205A	10370	CRES 316 COND A & B BAR	
	05617	GLASS TEMPERED (INORGANIC)	
	00016	TEFLON TFE	
10KA	00140	DELRIN ACETAL	WASHER
10LP-EU	10267	CRES A286	BOLT, LOCK
112	10515	STEEL 1055-1090 LOW CARBON	
113 THERMALLOY	60069	TEFLON	BUSHING
114-0567	10268	CRES 300 SERIES FASTENER MATL	
	10267	CRES A286 FASTENER MATL ONLY	
	00597	LUBE DRY	
1155001	00016	TEFLON TFE	
121007	10267	CRES A286 FASTENER MATL ONLY	
	10147	SPRING 17-7PH CH 900 WIRE STP	

MSFC-HDBK-527 REV F ■ 9999942 0006979 4 ■

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
12120-A-A-XX	10267	CRES A286 FASTENER MATL ONLY	
	10328	PLATING GOLD	
122069	10267	CRES A286 FASTENER MATL ONLY	
1230284-017	60127	INK MARKING STENCIL	SWITCH SENSITIVE
1262A-XXX	05498	ADHES SCOTCHWELD 2214HT AL FIL	
	30112	AL 2024-T3/T4 PLATE BAR TUBE	
	10321	BRASS, ALL FORM	
	10276	COATING ANODIC TYPE 1	
	10451	CRES 17-7PH COND C SHT & SP	
	05370	LUBE OIL DC-200 SILICONE	
	05278	RUBBER ETHYLENE PROPYLENE	
	10079	SOLDER SN 50/60/62/63	
	00016	TEFLON TFE	
1262T-XXX	10451	CRES 17-7PH COND C SHT & SP	
	30080	CRES 303 FREE MACHINING	
	20161	LUBE DRY 822	
	05370	LUBE OIL DC-200 SILICONE	
	05278	RUBBER ETHYLENE PROPYLENE	
	00016	TEFLON TFE	
13090	10469	CU WIRE SILVER PLATED	
	00016	TEFLON TFE	
	05548	TFE/ONE PERCENT CARBON BLACK	
	10733	WIRE - CU CLAD AG COATED	
132-0115-0002	10638	BE-CU ALLOY STRIP	
	10321	BRASS, ALL FORM	
	05729	CLAMP CUSH SIL/GLASS LAMIN JM	
	10620	CU 97.8CU 1PB 1NI .2P	
	10311	PLATING COPPER ELECTRO DEPOSIT	
	10328	PLATING GOLD	
	05660	TFE/25% GLASS	
	05759	TUBING RT-1146 VITON HS	
138-NN-5387	00019	NYLON PLASTIC	
143610-X-20	10100	CRES 347 ANN BAR SHP FRG WIRE	
	10158	NI HAST C ANN CSTG INV	
	00016	TEFLON TFE	
150-008-306-XXX	10268	CRES 300 SERIES FASTENER MATL	
150-046-306-XXX	10268	CRES 300 SERIES FASTENER MATL	
150500-12XX	10321	BRASS, ALL FORM	
	30080	CRES 303 FREE MACHINING	
	10501	CU RODS & SHAPES	
	10328	PLATING GOLD	
	02976	RUBBER SILICONE	
	05180	SLEEVING KYNAR/VITON E/S	
	00016	TEFLON TFE	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
150511-12XX	10271	BE-CU HT/AT BAR ROD WIRE FRG	
	30080	CRES 303 FREE MACHINING	
	10501	CU RODS & SHAPES	
	10328	PLATING GOLD	
	05180	SLEEVING KYNAR/VITON H/S	
	00016	TEFLON TFE	
150S	30080	CRES 303 FREE MACHINING	
	05204	RUBBER NITRILE (NRB)	
	00016	TEFLON TFE	
157	10321	BRASS, ALL FORM	
	10308	PLATING NICKEL ELECTRODEPOSIT	
160-2051	10321	BRASS ALL FORMS	SOLDER TERMINAL
	10039	PLATING SILVER	
1617623-XX	30080	CRES 303 BAR FRG FREE MACHINE	INSERT
1617829	10023	AL 6061-T6/651 RLD BAR SHP ROD	CONNECTOR RECEPTACLE
	50229	CRES 302 COND.B	
	10354	CU WIRE ALLOY 102	
	61239	MOLD CPD DAP FS6 CAF BLUE	
1617855	10321	BRASS, ALL FORMS	WIRE WRAP TERMINALS
	60299	TUBING POLYVINYLIDENE FLOUR HS	
1621163-5CD	10268	CRES 300 SERIES FASTENER MATL	WASHER
1621185	10350	CRES 301/302 ANN SHT STDS ONLY	WASHER
1621359-001	62629	INSUL GLASS BEADS	THERMISTOR,GLASS BEAD
	05179	INSUL WIRE AG PLATE TFE/POLYIM	
	03484	RUBBER RTV 566 SILICONE	
1621360-001	30121	CRES 17-7PH	TRANSDUCER
	20902	EEE PART	
	05179	INSUL WIRE AG PLATE TFE/POLYIM	
	05000	PRIMER SILANE SS4155	
	03484	RUBBER RTV 566 SILICONE	
1621409	30160	CRES 15-5PH H900	PIN
1621424-018	10267	CRES A286 FASTENER MATL SH	BOLT 7/16 HEX SELF-LOC
	05123	VESPEL SP-1/POLYIMIDE-CU	
1621443	10025	AL 6061-T6/62 DRWN SMLESS TUBE	FASTENER,PANEL STRUCTU
	10421	AL 7075-T73XX EXTRU BAR ROD WR	
	10267	CRES A286 FASTENER MATL SH	
	10281	PLATING SILVER,FASTENERS ONLY	
1621444	10025	AL 6061-T6/62 DRWN SMLESS TUBE	FASTENER,PANEL STRUCTU
	10421	AL 7075-T73XX EXTRU BAR ROD WR	
	10267	CRES A286 FASTENER MATL SH	
	10281	PLATING SILVER,FASTENERS ONLY	

MSFC-HDBK-527 REV F 9999942 0006981 2

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
1621490	10354	COPPER	HEATER,ELECTRICAL
	10039	PLATING SILVER	
	60422	POLY (AMIDE-IMIDE)	
17B-7-5	10328	PLATING GOLD	
	10149	SPRING BE-CU AT WIRE & STRIP	
185	10321	BRASS, ALL FORM	
	10322	BRONZE PHOSPHOR, ALL FORMS	
	10308	PLATING NICKEL ELECTRODEPOSIT	
191012	10267	CRES A286 FASTENER MATL ONLY	
191019-6-X	10267	CRES A286 FASTENER MATL ONLY	
192012	10267	CRES A286 FASTENER MATL ONLY	
192019	10267	CRES A286 FASTENER MATL ONLY	
194401	10090	CRES 304 ANN SHT PLT STRIP	
	10146	SPRING ELGILOY RC 55 WIRE STP	
195012	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
1985735	30044	BERYLLIUM OXIDE	TRANSISTOR INSUL DISC
1HM25	10339	BRAZE 92.5 AG 7.2 CU .22 LI	
	10247	BRAZE CU WIRE	
	10382	CRES 302 ANN BAR SHP FRG WIRE	
	30080	CRES 303 FREE MACHINING	
	10475	CRES 305 SHEET & STRIP	
	10100	CRES 347 ANN BAR SHP FRG WIRE	
	30134	GLASS SEALING ALLOY 52	
	10264	SPRING TEMPER 15-7M0 RH950	
	10314	STEEL INVAR 36 BAR	
	10358	STEEL SAE/AISI 1008-1010	
1RL6	10370	CRES 316 COND A & B BAR	
	05617	GLASS TEMPERED (INORGANIC)	
	00016	TEFLON TFE	
2-21253K0322	05208	MOLD CPD 4203 TORLON	BLANKET FASTENER
	60069	TEFLON	
2-21255K0323	60069	TEFLON TFE	BLANKET THERMAL DISC
2-XXX	60643	RUBBER VITON V747-75	O-RING
20 000 72	10221	BRASS	SOLDER TERMINAL
	10213	COPPER	
20273	10233	CRES 304L ANN BAR & FRG STK VM	
	10098	CRES 321 ANN BAR SHP FRG WIRE	
	00016	TEFLON TFE	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
2054-1201-02	10271	BE-CU HT/AT BAR ROD WIRE FRG	
	10506	CRES 303/304 BAR AND WIRE	
	10328	PLATING GOLD	
	00016	TEFLON TFE	
2054-1221-02	10271	BE-CU HT/AT BAR ROD WIRE FRG	
	10155	CRES 304L/304 ANN STL CSTG	
	10328	PLATING GOLD	
	00016	TEFLON TFE	
207065	10294	CRES 302 ANN THRU 1/2 HD PT SH	
212-12S	10262	CRES 302	HOLDING PIN/RECEPTACLE
21A	10370	CRES 316 COND A & B BAR	
	00016	TEFLON TFE	
21L1-XXX	10267	CRES A286 FASTENER MATL ONLY	WASHER,FLAT
	50124	PLATING CADMIUM	
21L2-XX-XX	30108	AL 2024-T3/T4 FASTENERS ONLY	SPACERS,RIVET
21L2AXX-XX	30108	AL 2024-T3/T4 FASTENERS ONLY	SPACERS,RIVET
	10276	COATING ANODIC TYPE 1	
21L3-XXX	10267	CRES A286 FASTENER MATL ONLY	WASHER,OVERSIZE
	50124	PLATING CADMIUM	
21L3-XXXP	10267	CRES A286 FASTENER MATL ONLY	WASHER,OVERSIZE
21L4-XXX	10267	CRES A286 FASTENER MATL ONLY	WASHER,OVERSIZE
	50124	PLATING CADMIUM	
21L4-XXXP	10267	CRES A286 FASTENER MATL ONLY	WASHER,OVERSIZE
22 759/17	05205	TEFZEL (ETFE)	WIRE
22L1-XX-XX	10267	CRES A286 FASTENER MATL ONLY	PIN,HEADLESS
	50124	PLATING CADMIUM	
22L2-XX-XXX	10267	CRES A286 FASTENER MATL ONLY	PIN,HEADED
	50124	PLATING CADMIUM	
22L3-1	10508	AL 2024-T851/T8511 BAR	PIN,TOGGLE
	50056	AL 2024-T8XX SHEET	
	10277	COATING ANODIC TYPE 2	
22L4XXX	10267	CRES A286 FASTENER MATL ONLY	PIN,STRAIGHT
	50124	PLATING CADMIUM	
22L5-XX	10267	CRES A286 FASTENER MATL ONLY	KEY,WOODRUFF
	50124	PLATING CADMIUM	
23306-XA	50243	CUPAL 20% CU 80% AL	WASHER

MSFC-HDBK-527 REV F ■ 9999942 0006983 6 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
24502A	10088	CRES 301 ANN THRU 1/2 HD PT SH	
	10294	CRES 302 ANN THRU 1/2 HD PT SH	
	10100	CRES 347 ANN BAR SHP FRG WIRE	
	10099	CRES 347 ANN SHT PLT STRIP	
	10267	CRES A286 FADTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
24540	10268	CRES 300 SERIES FASTENER MATL	
	10097	CRES 321 ANN SHT PLT STRIP	
	10100	CRES 347 ANN BAR SHP FRG WIRE	
	30149	CRES 400 SERIES	
24BSS	50059	CRES 316 ANN TO 1/2 HD SH PL	NUT,COUPLING
24TSS	50059	CRES 316 ANN TO 1/2 HD SH PL	SLEEVE
256-7493	10321	BRASS, ALL FORM	
	05479	FABRIC HT-90-40 NOMEX	
259T1-XXX	10370	CRES 316 COND A & B BAR	
	05668	RUBBER NITRILE	
	10148	SPRING 302 COND B WIRE	
25L1-XX-XX	50084	CRES A286 180 KSI BAR FRG TB	PIN,PROTRUD HEAD
	50124	PLATING CADMIUM	
25L10-XX-XX	10222	MONEL 400/405	RIVET,BLIND
	50124	PLATING CADMIUM	
25L11-XX-XX	10222	MONEL 400/405	RIVET,BLIND
	50124	PLATING CADMIUM	
25L12-XX-XX	10335	AL 2117-T4 ANN WIRE (RIVETS)	RIVET,SOLID
	00666	CTNG CONVERSION CHROMATE	
25L13-XX-XX	10267	CRES A286 FASTENER MATL ONLY	RIVET,SEMI-TUBLR
	50124	PLATING CADMIUM	
25L14-XX-XX	10267	CRES A286 FASTENER MATL ONLY	RIVET,SEMI-TUBLR
	50124	PLATING CADMIUM	
25L22-XX-XX	10123	MULTIPHASE MP35N	PIN,PROTRUDING
	50124	PLATING CADMIUM	
25L24-XX	10023	AL 6061-T6/651 RLD BAR SHP	COLLAR,6061-T6
	60059	CETYL ALCOHOL	
	10277	COATING ANODIC TYPE 2	
25L25-8	10023	AL 6061-T6/651 RLD BAR SHP	COLLAR,REMOVABLE
	60059	CETYL ALCOHOL	
	10277	COATING ANODIC TYPE 2	
25L26-3-X	60059	CETYL ALCOHOL	RIVET,PULL-THRU
	10336	CRES 305 ANN BAR	
	10267	CRES A286 FASTENER MATL ONLY	
	05638	LUBE TRANSLUBE 20204	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
25L26-3-X	50124	PLATING CADMIUM	RIVET,PULL-THRU
25L27-3-X	60059	CETYL ALCOHOL	RIVET,PULL-THRU
	10336	CRES 305 ANN BAR	
	10267	CRES A286 FASTENER MATL ONLY	
	05638	LUBE TRANSLUBE 20204	
	50124	PLATING CADMIUM	
25L3-XX-XX	50084	CRES A286 180 KSI BAR FRG TB	PIN,100 DEG HEAD
	50124	PLATING CADMIUM	
25L5-XX	10292	AL 2024-T6 BAR ROD WIRE	COLLAR,ALUMINUM
	60059	CETYL ALCOHOL	
	10277	COATING ANODIC TYPE 2	
25L5-XXW	10292	AL 2024-T6 BAR ROD WIRE	COLLAR,ALUMINUM
	50055	AL 2024-T6 SHEET	
	10277	COATING ANODIC TYPE 2	
	05167	LUBE,DRYLUBE 701/702	
25L6-XX	60059	CETYL ALCOHOL	COLLAR,A-286
	10267	CRES A286 FASTENER MATL ONLY	
	50124	PLATING CADMIUM	
25L6-XXW	10268	CRES 300 SERIES FASTENER MATL	COLLAR,A-286
	10267	CRES A286 FASTENER MATL ONLY	
	05167	LUBE,DRYLUBE 701/702	
	50124	PLATING CADMIUM	
25L8-XX	10297	AL 2024-T6 BAR ROD WIRE	COLLAR,ALUMINUM
	10277	COATING ANODIC TYPE 2	
	10267	CRES A286 FASTENER MATL ONLY	
	05167	LUBE,DRYLUBE 701/702	
	50124	PLATING CADMIUM	
25L9-XX	10267	CRES A286 FASTENER MATL ONLY	COLLAR,A-286
	05167	LUBE DRILUBE 701/702	
	50124	PLATING CADMIUM	
26 S39	10470	CARBON STEEL	CROSS SLOTTED SCREW
262T1-XXX	10370	CRES 316 COND A & B BAR	
	01455	RUBBER E515-8 EPR	
	10148	SPRING 302 COND B WIRE	
2673001601	50234	MANGANESE ZINC BEADS	BEADS SHIELD
26L1-XXXXX	50084	CRES A286 180KSI BAR FRG TB	BOLT,INT WRENCH
	50124	PLATING CADMIUM	
26L10-XX-XX	50084	CRES A286 180KSI BAR FRG TB	BOLT,BLIND
	50124	PLATING CADMIUM	
26L12-4-XX	10023	AL 6061-T6/651 RLD BAR SHP	SCREW,CAPTIVE
	10276	COATING ANODIC TYPE 1	
	10382	CRES 302 ANN BAR SHP FRG WIRE	

MSFC-HDBK-527 REV F ■ 9999942 0006985 T ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
26L12-4-XX	10262	CRES 302 HARD SHT PLT STRIP	SCREW,CAPTIVE
	10267	CRES A286 FASTENER MATL ONLY	
	50124	PLATING CADMIUM	
	10148	SPRING 302 COND B WIRE	
26L13-XX-XXX	50084	CRES A286 180KSI BAR FRG TB	BOLT,HEX HEAD
	50124	PLATING CADMIUM	
26L14-XXLXXX	10267	CRES A286 FASTENER MATL ONLY	FASTENER,BLIND
	50124	PLATING CADMIUM	
26L15-XX-XX	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
	50124	PLATING CADMIUM	
26L16-XXLXXX	10267	CRES A286 FASTENER MATL ONLY	FASTENER,BLIND
	50124	PLATING CADMIUM	
26L17-XX-XX	10267	CRES A286 FASTENER MATL ONLY	SCREW,HEX HEAD
	50124	PLATING CADMIUM	
26L18-XX	10023	AL 6061-T6/651 RLD BAR SHP	WELDING STUD
26L2-XXXXX	50084	CRES A286 180KSI BAR FRG TB	BOLT,EXT WRENCH
	50124	PLATING CADMIUM	
26L20-XXPXX	10267	CRES A286 FASTENER MATL ONLY	BOLT,FLUSH HEAD
	50124	PLATING CADMIUM	
26L21-XX-XX	10305	MULTIPHASE MP35N BAR	BOLT,SHEAR HEAD
	50124	PLATING CADMIUM	
26L23PXXXXX	50084	CRES A286 180KSI BAR FRG TB	BOLT,12 POINT
26L24-4-XX	10023	AL 6061-T6/651 RLD BAR SHP	SCREW,CAPTIVE
	10276	COATING ANODIC TYPE 1	
	10382	CRES 302 ANN BAR SHP FRG WIRE	
	10262	CRES 302 HARD SHT PLT STRIP	
	10267	CRES A286 FASTENER MATL ONLY	
	50124	PLATING CADMIUM	
	10148	SPRING 302 COND B WIRE	
26L2PXXXXX	50084	CRES A286 180KSI BAR FRG TB	BOLT,EXT WRENCH
26L3-XXXXX	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
	50124	PLATING CADMIUM	
26L4-XXXXX	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
	50124	PLATING CADMIUM	
26L6-XXXXX	10267	CRES A286 FASTENER MATL ONLY	STUD,LOCKED IN
	50124	PLATING CADMIUM	
26L8-XX-XX	10305	MULTIPHASE MP35N BAR	BOLT,SHEAR,MP35N
	50124	PLATING CADMIUM	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
26L9-XX-XX	50084	CRES A286 180KSI BAR FRG TB	BOLT,BLIND
	50124	PLATING CADMIUM	
2700-0035	10693	CRES 17-4PH H1075	FITTING BRAZE
2774-0049	50059	CRES 316	PIN,FITTING END
2774-0050	05130	KEL-F CTFE	LOCK PLUG
27C	10268	CRES 300 SERIES FASTENER MATL	
	10281	PLATING SILVER,FASTENERS ONLY	
27L2-1	10268	CRES 300 SERIES FASTENER MATL	CABLE,STEEL
	10514	CRES CABLE 300 SERIES	
27L3-1	10268	CRES 300 SERIES FASTENER MATL	CABLE,STEEL
	10514	CRES CABLE 300 SERIES	
2800-0013	10430	CRES 17-4PH H1075	PRESS CAP ASSEMBLY
2800-0016-1	30188	AL ALLOY ALCOA 5652	NAMEPLATE
2811-0242	10454	AL 7075-T73	NUT JAM
2811-0244-1	10043	AL 7075-T73	ELBOW,90 FLARED TUBE
	10276	ANODIC-TYP 1	
28L1-4-XX	10267	CRES A286 FASTENER MATL ONLY	FASTENER,QK/RLSE
	50124	PLATING CADMIUM	
28L1-50	10088	CRES 301 ANN THRU 1/2 HARD	RETAINER,SPRING
	50124	PLATING CADMIUM	
	10146	SPRING ELGILOY RC55 WIRE STP	
28L2-4	10267	CRES A286 FASTENER MATL ONLY	FASTENER,QK/RLSE
	00881	LUBE DRY EVERLUBE 812	
	50124	PLATING CADMIUM	
	10146	SPRING ELGILOY RC55 WIRE STP	
301-122440-02	00019	NYLON PLASTIC	
304140	10443	AL 5056	RIVET
304XXX	10443		RIVET
305XXX	10443	AL 5056	RIVET
311P405	99011	SEE FILE FOR MATERIALS	
328854	10333	CU SHT PLT BAR ANN	
	10308	PLATING NICKEL ELECTRODEPOSIT	
	00016	TEFLON TFE	
328855	10333	CU SHT PLT BAR ANN	
	10308	PLATING NICKEL ELECTRODEPOSIT	
	00016	TEFLON TFE	

MSFC-HDBK-527 REV F 9999942 0006987 3

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
328856	10333	CU SHT PLT BAR ANN	
	10308	PLATING NICKEL ELECTRODEPOSIT	
	00016	TEFLON TFE	
328857	10333	CU SHT PLT BAR ANN	
	10308	PLATING NICKEL ELECTRODEPOSIT	
	00016	TEFLON TFE	
328858	10333	CU SHT PLT BAR ANN	
	10308	PLATING NICKEL ELECTRODEPOSIT	
	00016	TEFLON TFE	
328859	10333	CU SHT PLT BAR ANN	
	10308	PLATING NICKEL ELECTRODEPOSIT	
	00016	TEFLON TFE	
328860	10333	CU SHT PLT BAR ANN	
	10308	PLATING NICKEL ELECTRODEPOSIT	
	00016	TEFLON TFE	
328861	10333	CU SHT PLT BAR ANN	
	10308	PLATING NICKEL ELECTRODEPOSIT	
	00016	TEFLON TFE	
32L1XXXXXXXXXX	10431	CRES 300 SERIES NON-FREE MACH	HOSE ASSY FLEX
	10289	CRES 321/347 ANN SHT STDS	
	10455	CRES 347 COND A & B WIRE	
	05167	LUBE DRYLUBE 701/702	
32L2XXXXXXXXXX	10431	CRES 300 SERIES NON-FREE MACH	HOSE ASSY FLEX
	10289	CRES 321/347 ANN SHT STDS	
	10455	CRES 347 COND A & B WIRE	
	05167	LUBE DRYLUBE 701/702	
32L3-X	10431	CRES 300 SERIES NON-FREE MACH	HOSE ASSY FLEX
	10510	CRES 304L/321/347/316 ANN TB	
	05167	LUBE DRYLUBE 701/702	
	05710	PAPER NOMEX (ARAMID)	
	00649	TEFLON, FEP	
32L4XXXXXXXXXX	10431	CRES 300 SERIES NON-FREE MACH	HOSE ASSY FLEX
	10510	CRES 304L/321/347/316 ANN TB	
	05167	LUBE DRYLUBE 701/702	
	05710	PAPER NOMEX (ARAMID)	
	00649	TEFLON, FEP	
32L5-1	10391	CRES 302/304/316 SHT PLT WIRE	HOSE ASSY
	10351	CRES 304 ANN BAR SHP FRG WIRE	
	00016	TEFLON, TFE	
	10520	WIRE 302 CRES OR 305 CRES	
32XXXX	10333	CU SHT PLT BAR ANN	
	10308	PLATING NICKEL ELECTRODEPOSIT	
	00016	TEFLON TFE	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
338360	10171	AL 5052	NUT
33L1-XX	10267 50124	CRES A286 FASTENER MATL ONLY PLATING CADMIUM	NUT,SELF LOCKING
33L10-1	10097 10267 50124	CRES 321 ANN SHT PLT STRIP CRES A286 FASTENER MATL ONLY PLATING CADMIUM	NUT,GANG CHANNEL
33L12-4	10088 10351 10267 50124	CRES 301 ANN THRU 1/2 HARD CRES 304 ANN BAR SHP FRG WIRE CRES A286 FASTENER MATL ONLY PLATING CADMIUM	NUT PLATE,CORNER
33L13-X	10267 50124	CRES A286 FASTENER MATL ONLY PLATING CADMIUM	NUT,HOOK,S/LOCK
33L14-XX	10305 50124	MULTIPHASE MP35N BAR PLATING CADMIUM	NUT,SELF LOCKING
33L15LXX	10267 50124	CRES A286 FASTENER MATL ONLY PLATING CADMIUM	TE,S/LOCK
33L16-4	10267 50124	CRES A286 FASTENER MATL ONLY PLATING CADMIUM	NUT PLATE,CORNER
33L2-XX	10267 50124	CRES A286 FASTENER MATL ONLY PLATING CADMIUM	NUT,SELF LOCKING
33L3-XX	10267 50124	CRES A286 FASTENER MATL ONLY PLATING CADMIUM	NUT PLATE,S/LOCK
33L4-XX	10267 50124	CRES A286 FASTENER MATL ONLY PLATING CADMIUM	NUT PLATE,S/LOCK
33L6-XX	10267 50124	CRES A286 FASTENER MATL ONLY PLATING CADMIUM	NUT,SLOTTED,HEX
33L7-XX	10267 50124	CRES A286 FASTENER MATL ONLY PLATING CADMIUM	NUT,PLAIN,HEX
33L9-XX	10267 50124	CRES A286 FASTENER MATL ONLY PLATING CADMIUM	NUT,DOME,S/LOCK
34022644	10315	CRES 302 WIRE	STUD
34L1-XXXX	10268 50124	CRES 300 SERIES FASTENER MATL PLATING CADMIUM	INSERT,MINIATURE
34L2-XXXX	10091 50124 10148	CRES 304 COND B BAR SHP PLATING CADMIUM SPRING 302 COND B WIRE	INSERT,HEAVY DY
34L3-XXXX	10091 50124 10148	CRES 304 COND B BAR SHP PLATING CADMIUM SPRING 302 COND B WIRE	INSERT,FLOATING

MSFC-HDBK-527 REV F 9999942 0006989 7

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
34L6-XX	10267	CRES A286 FASTENER MATL ONLY	SLEEVE,PROTRUDE
	50124	PLATING CADMIUM	
34L7-X	10267	CRES A286 FASTENER MATL ONLY	SLEEVE,PROTRUDE
	50124	PLATING CADMIUM	
36L1-X	50084	CRES A286 180KSI BAR FRG TB	BEARING,PLAIN
	20397	LUBE DRY MOLYKOTE M-8800	
	10406	NI INCONEL 718 BAR FRG	
	50124	PLATING CADMIUM	
	10275	PLATING CHROMIUM (CLASS 2)	
36L10-X	05042	LUBE DRY VITROLUBE 1220	BEARING,PLAIN
	10406	NI INCONEL 718 BAR FRG	
36L11-1	05042	LUBE DRY VITROLUBE 1220	BEARING,ROD END
	10406	NI INCONEL 718 BAR FRG	
36L12-1	50084	CRES A286 180KSI BAR FRG TB	BEARING,PLAIN
	05042	LUBE DRY VITROLUBE 1220	
	10406	NI INCONEL 718 BAR FRG	
36L2-X	50084	CRES A286 180KSI BAR FRG TB	BEARING,PLAIN
	05042	LUBE DRY VITROLUBE 1220	
	10406	NI INCONEL 718 BAR FRG	
	50124	PLATING CADMIUM	
	10275	PLATING CHROMIUM (CLASS 2)	
36L3-XX-XXX	10351	CRES 304 ANN BAR SHP FRG WIRE	BUSHING,PLAIN
	50124	PLATING CADMIUM	
36L4-XX-XXX	10351	CRES 304 ANN BAR SHP FRG WIRE	BUSHING,FLANGED
	50124	PLATING CADMIUM	
36L8-XC	50084	CRES A286 180KSI BAR FRG TB	BEARING,PLAIN
	05042	LUBE DRY VITROLUBE 1220	
	10406	NI INCONEL 718 BAR FRG	
	50124	PLATING CADMIUM	
36L9-X	50084	CRES A286 180KSI BAR FRG TB	BEARING,PLAIN
	05042	LUBE DRY VITROLUBE 1220	
	10406	NI INCONEL 718 BAR FRG	
36L9-XC	50084	CRES A286 180KSI BAR FRG TB	BEARING,PLAIN
	05042	LUBE DRY VITROLUBE 1220	
	10406	NI INCONEL 718 BAR FRG	
	50124	PLATING CADMIUM	
400-C-316	10370	CRES 316 COND A & B BAR	
40M39569	10337	AL 6061	CONNECTOR
	10149	COPPER	
	50232	COPPER, LEAD ANACONDA #129	
	10506	CRES 303	
	10475	CRES 305	
	10634	CU, LEAD NICKEL ANACONDA 7021	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
40M50578	05275	INSUL WIRE TFE	
	10223	NI COATED CU/NICKEL WIRE	
4171569-001	06443	ADHES POLYESTER ETC-1	SHIM
	10366	AL 1100 ANN SHEET	
4171569-003	06443	ADHES POLYESTER ETC-1	SHIM
	10366	AL 1100 ANN SHEET	
4171569-005	06443	ADHES POLYESTER ETC-1	SHIM
	10366	AL 1100 ANN SHEET	
4171569-007	06443	ADHES POLYESTER ETC-1	SHIM
	10366	AL 1100 ANN SHEET	
4171702-001	50064	CRES 440A/440B/440C RC58-65	PIN
4172726-001	61482	LAMIN B10-108-63 CLASS EPOXY	MULTILAYER BOARD
	61489	LAMIN GLASS/EPOXY W/CU	
4173115-501	10389	CRES 15-5PH H1025 BAR & FORG	PIN
	10281	PLATING SILVER	
	60434	POLYIMIDE-CU	
41L1XXX-XX	10098	CRES 321 ANN BAR SHP FRG WIRE	CONDUIT ASSEMBLY
	10097	CRES 321 ANN SHT PLT STRIP	
42L1-XA	10023	AL 6061-T6/651 RLD BAR SHP	HANDLE,U SHAPE
	10277	COATING ANODIC TYPE 2	
42L1-XC	10351	CRES 304 ANN BAR SHP FRG WIRE	HANDLE,U SHAPE
43L1-X	05124	LAMIN GLASS/POLIMIDE	PLUG,NON-METAL
45104	10399	CRES 17-4PH H1025 BAR FRG RING	
4553	10321	BRASS	SOLDERING PIN
	10029	SOLDER PLATED	
4570	10321	BRASS	TERMINAL PC BOARD
	10079	SOLDER PLATED	
4571	10321	BRASS	TERMINAL PC BOARD
	10079	SOLDER PLATED	
4572	10321	BRASS	TERMINAL PC BOARD
	10079	SOLDER PLATED	
45L1-XXC	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP,CUSH
	50124	PLATING CADMIUM	
	00016	TEFLON TFE	
45L2-XXC	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,SADDLE,CSH
	50124	PLATING CADMIUM	
	00016	TEFLON TFE	

MSFC-HDBK-527 REV F 9999942 0006991 5

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
45L4-200	10267	CRES A286 FASTENER MATL ONLY	COUPLING,CLAMP
	50124	PLATING CADMIUM	
	10281	PLATING SILVER,FASTENERS ONLY	
45L5-XX	10294	CRES 302 ANN THRU 1/2 HARD	CLAMP,LOOP TYPE
45L5PXX	10294	CRES 302 ANN THRU 1/2 HARD	CLAMP,LOOP TYPE
	50124	PLATING CADMIUM	
45L7-412	10268	CRES 300 SERIES FASTENER MATL	CLAMP,T-BOLT
	50167	CRES 321 COND 1/4 OR 1/2 HARD	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENER ONLY	
45L8-XX	02997	CLAMP CUSHION SILICONE/GLASS	CLAMP,LOOP,CUSH
	10294	CRES 302 ANN THRU 1/2 HARD	
	50167	CRES 321 COND 1/4 OR 1/2 HARD	
	50124	PLATING CADMIUM	
45L9-XX	02997	CLAMP CUSHION SILICONE/GLASS	CLAMP,SADDLE,CSH
	10294	CRES 302 ANN THRU 1/2 HARD	
	50167	CRES 321 COND 1/4 OR 1/2 HARD	
	50124	PLATING CADMIUM	
45XX USECO	05352	ALUM (AL2O3)	TERMINAL
	05369	DIALYPHTHALATE (DAP)	
	60069	TEFLON (PTFE)	
47L1-X	10306	CRES 304L ANN BAR SHP FRG	VALVE,CHECK
	10148	SPRING 302 COND B WIRE	
	60068	TEFLON TFE	
47XX USECO	05352	ALUM (AL2O3)	TERMINAL
	05369	DIALYPHTHALATE (DAP)	
	60069	TEFLON (PTFE)	
480	10370	CRES 316 COND A & B BAR	
4814-1	10321	BRASS	SOLDER TERMINAL
48L1-1	10306	CRES 304L ANN BAR SHP FRG	FILTER,IN-LINE
	10318	CRES 304L/316L WIRE/SCRN/CLOTH	
	10011	CRES A286 140KSI BAR FRG TBNG	
	06029	CTNG 850-204/855-225/856-204	
4BTX-SS	10370	CRES 316 COND A & B BAR	NUT,TRIPPLE LOX
4C2661-2	10416	CRES 17-4PH H1150 BAR ROD FRG	
4TX-SS	10370	CRES 316 COND A & B BAR	SLEEVE,TX
5 LA 105	10124	CRES A286	NUT,FLOATING
	10039	PLATING SILVER	
5 SL 563	05232	RUBBER SILICONE	O'RING

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
5 SMF 5209 M	10124	CRES A286	NUT,FLOATING
	10039	PLATING SILVER	
50.061	10430	CRES 17-4PH	COUPLING
50.130	10430	CRES 17-4PH	FITTING
50007	10430	CRES 17-4PH	FITTING
51 L1	10382	CRES 302	FASTNER
51 L7	10382	CRES 302	HOOK
512222B0160H	10024	AL 6061-T6/T6511 EXT BR SHP TB	
	10277	COATING ANODIC TYPE 2	
	00777	FABRIC FIBERGLAS (INORGANIC)	
	00016	TEFLON TFE	
	01596	THREAD NOMEX	
5162-T1	10370	CRES 316 COND A & B BAR	
	05278	RUBBER ETHYLENE PROPYLENE	
	10147	SPRING 17-7PH CH900 WIRE STP	
5171200	10268	CRES 300 SERIES	UNION
5171204	10268	CRES 300 SERIES	UNION
51L3-1	10262	CRES 302 HARD SHT PLT STRIP	RING,RETAINING
5202-04AH-E12	10399	CRES 17-4PH H1025 BAR FRG RING	
	10409	SPRING 17-7 CH900 PLT SHT ST	
	10147	SPRING 17-7PH CH900 WIRE STP	
	00016	TEFLON TFE	
52757	10088	CRES 301 ANN THRU 1/2 HD PT SH	
	10087	CRES 301 FUL HD PLT SHT STRIP	
	10262	CRES 302 HARD SHEET PLT STRIP	
	10097	CRES 321 ANN SHT PLT STRIP	
	10100	CRES 347 ANN BAR SHP FRG WIRE	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
53080	30099	AL 2017 ALL TEMPERS	
	30112	AL 2024-T3/T4 PLATE BAR TUBE	
	10276	COATING ANODIC TYPE 1	
	30123	CRES 17-4 H9XX BAR CST	
	30124	CRES 17-4PH H900/15-7MO TH1050	
	10516	CRES 17-7PH COND C/302 COND B	
	10294	CRES 302 ANN THRU 1/2 HD PT SH	
	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	05128	LUBE GREASE BRAYCO 3L-38RP	
53611	10636	AL 380 CASTING	
	10277	COATING ANODIC TYPE 2	
	10431	CRES 300 SERIES NON-FREE MACH	

MSFC-HDBK-527 REV F 9999942 0006993 9

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
53611	30080	CRES 303 FREE MACHINING	
	10011	CRES A286 140KSI BAR FRG TBNG	
	00395	LUBE DRY N350 A PHENOLIC BINDR	
	10148	SPRING 302 COND B WIRE	
53612	10728	BRAZE 50AG 16CU 15ZN 3NI	
	10431	CRES 300 SERIES NON-FREE MACH	
	10011	CRES A286 140 KSI BAR FRG TBNG	
5416K26H-SS	10431	CRES 300 SERIES NON-FREE MACH	
	30120	CRES 431 BAR SHP FRG	
54621	30099	AL 2017 ALL TEMPERS	
	10022	AL 6061-T6/62/651 SHT PLT	
	10024	AL 6061-T6/T6511 EXT BR SHP TB	
	10321	BRASS, ALL FORM	
	10276	COATING ANODIC TYPE 1	
	05416	CTNG CONVERSION BLACK OXIDE	
54L1-XX	10220	CRES 304 ANN WIRE	MOUNT,SLIDE
	10092	CRES 304L ANN SHT PLT STRIP	
	05331	FABRIC TFE COATED	
54L2-X	00895	ADHES DC 281/282	STRIP,RUBBER
	05143	RUBBER SILICONE	
54L4-1	10351	CRES 304 ANN BAR SHP FRG WIRE	ON ISOLTR
	10381	CRES 304L/316L/321/347 ANN SHT	
	10220	CRES 004 ANN WIRE	
	10645	SPRING 304 WIRE FULL HARD	
54L5-1	10375	CRES 304 ANN THRU 1/2 HARD	VIBRATION ISOLTR
	10267	CRES A286 FASTENER MATL ONLY	
	10514	CRES CABLE 300 SERIES	
54L6-X	10508	AL 2024-T851/T8511 BAR	VIBRATION ISOLTR
	10321	BRASS, ALL FORMS	
	00666	CTNG CONVERSION CHROMATE	
	10308	PLATING NICKEL ELECTRODEPOSIT	
	30143	PLATING ZINC	
	05433	RUBBER NEOPRENE ASTM D2000	
	10358	STEEL SAE 1010	
559T-1M-XX	30080	CRES 303 FREE MACHINING	
	05002	RUBBER NITRILE	
	10148	SPRING 302 COND B WIRE	
55L2-X	10405	NI INCO 718 1950 ST SHT PLT	SEAL ASSEMBLY
	60069	TEFLON PTFE	
55L3-X	10405	NI INCO 718 1950 ST SHT PLT	SEAL ASSEMBLY
	60069	TEFLON PTFE	
55L4-XXXX	10147	SPRING 17-7PH CH900 WIRE STP	SEAL ASSEMBLY
	00649	TEFLON FEP	

MSFC-HDBK-527 REV F ■ 9999942 0006994 0 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
55L5-XXR	10011	CRES A286 140 KSI BAR FRG	SEAL,BOSS
	06029	CTNG 850-204/855-225/856-204	
55L6-XT	06029	CTNG 850-204/855-225/856-204	SEAL,FLANGE
	10407	NI INCO 718 1750 ST SHT PLT	
55L7-XXX	10087	CRES 301 FULL HARD PLT SHT	SEAL,ASSY,ROD
	00016	TEFLON TFE	
568-908-1235-70	05291	RUBBER 1235-70 SILICONE	
570-2045	10321	BRASS	INSULATED TERMINAL
	60266	CERAMIC SLEEVING	
	61738	PUTTY ALKYD #413	
5723-XXP	10294	CRES 302 ANN THRU 1/2 HD PT SH	
57979-3	10100	CRES 347 ANN BAR SHP FRG WIRE	
	10281	PLATING SILVER,FASTENERS ONLY	
57L1-XX-XXX	10351	CRES 304 ANN BAR SHP FRG WIRE	UNION,TB ORIFICE
57L10-XX	10351	CRES 304 ANN BAR SHP FRG WIRE	NUT,PLAIN,HEX
57L12J4-2	10351	CRES 304 ANN BAR SHP FRG WIRE	REDUCER,TUBE
	10370	CRES 316 COND A & B BAR	
57L3-XXX	10022	AL 6061-T6/62/651 SHT PLT	FLANGE,DUCT,40DEG
57L6-XXD	10508	AL 2024-T851/T8511 BAR	FITTING,ADAPTER
	10277	COATING ANODIC TYPE 2	
57L6-XXJ	10351	CRES 304 ANN BAR SHP FRG WIRE	FITTING,ADAPTER
57L7-XXD	10508	AL 2024-T851/T8511 BAR	FITTING,PG & BLR
	10277	COATING ANODIC TYPE 2	
57L7-XXJ	10351	CRES 304 ANN BAR SHP FRG WIRE	FITTING,PG & BLR
57L8-XX	10351	CRES 304 ANN BAR SHP FRG WIRE	NUT,COUPLING
	05370	LUBE DRILUBE 701	
57L9-XX	10351	CRES 304 ANN BAR SHP FRG WIRE	CAP ASSEMBLY
	05370	LUBE DRILUBE 701	
58L1-X	10363	NI BAR FLT WIRE STRIP	SPLICE,CONDUCTOR
58L2-XXXXX	50114	CU TERMINAL LUG & SPLICE	JUMPER ASSEMBLY
	10353	CU TUBE ANN NI PLATED SPLICE	
	10354	CU WIRE ELECTRICAL CONDUCTOR	
	10256	SPRING BE-CU COND A WIRE	
58L3-XXX	10353	CU TUBE ANN NI PLATED SPLICE	FERRULE,INNER
58L4-XXXX	10353	CU TUBE ANN NI PLATED SPLICE	FERRULE,OUTER

MSFC-HDBK-527 REV F ■ 9999942 0006995 2 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
58L5-XXXXX	10354	CU WIRE ELECTRICAL CONDUCTOR	JUMPER ASSEMBLY
	10363	NI BAR FLT WIRE STRIP	
58L6-XXXXX	50114	CU TERMINAL LUB & SPLICE	JUMPER ASSEMBLY
	10353	CU TUBE ANN NI PLATED SPLICE	
	10354	CU WIRE ELECTRICAL CONDUCTOR	
	05332	INSUL WIRE FEP/POLYIMIDE	
	10256	SPRING BE-CU COND A WIRE	
58L7-XX	02151	TUBING TFE HST	S&F SEALING ASSY
601296	05809	CTNG QR-4-3117/XY176 SILICONE	
	10384	NI INCO 718 ST/STA BAR	
	20105	POTTG CPD SYLGARD 182 SILICONE	
60XX-B-GXX	06225	INSUL WIRE FIBERGLAS INSUL	
	10223	NI COATED CU/NICKEL WIRE	
61170-XXXX	10267	CRES A286 FASTENER MATL ONLY	NUT,SELF-LOCKING
	10281	PLATING SILVER,FASTENER ONLY	
61170CXXXX	10267	CRES A286 FASTENER MATL ONLY	NUT,SELF-LOCKING
	50124	PLATING CADMIUM	
63151-4	10391	CRES 302/304/316 SHT PLT WIRE	
63151-6	30080	CRES 303 FREE MACHINING	
63152-X	10430	CRES 17-4PH H1075 BAR	
635	10308	PLATING NICKEL ELECTRODEPOSIT	
	10648	STEEL 1008-1020	
63761-XXX	10022	AL 6061-T6/62/651 SHT PLT	
	10268	CRES 300 SERIES FASTENER MATL	
	10267	CRES A286 FASTENER MATL ONLY	
	00666	CTNG CONVERSION CHROMATE	
64KS3	10336	CRES 305 ANN BAR	
66L1-X	10279	AL 11XX-0/HXX PLATE SHEET	BAND,MARKER
	10345	AL 3003-H14 PLATE SHEET	
6DC-C6	30111	AL 2024-T4	COLLAR
6DC-EUXXC	10267	CRES A286 FASTENER MATL ONLY	COLLAR
7008MS-160-T	05342	BUNA-N	G-T RING (SEAL)
	00016	TFE TEFLON	
7011MS-160-T	05342	BUNA-N	G-T RING (SEAL)
	00016	TFE TEFLON	
7017MS-160-T	05342	BUNA-N	G-T RING (SEAL)
	00016	TFE TEFLON	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
7017MS-5708	05342	BUNA-N	G-T RING SEAL
	00016	TFE TEFLON	
71 6165	10348	AL 11XX ANN FOIL	
	10277	COATING ANODIC TYPE 2	
	05173	TAPE 465/467/468 ACRYLIC FILM	
7113FR-160-T	01784	BUNA-N	G-T RING
	00016	TFE TEFLON	
7325M-160-T	05342	BUNA-N	G-T RING (SEAL)
	00016	TFE TEFLON	
73783CS	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
75462-XX-XX	50102	MULTIPHASE MP35N PASSIVATED	BOLT,TENSION
7631600C	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
76386	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
76540-XXXX	00597	LUBE DRY	NUT,SELF-LOCKING
	50102	MULTIPHASE MP35N PASSIVATED	
	10281	PLATING SILVER,FASTENERS ONLY	
76540CXXXX	00597	LUBE DRY	NUT,SELF-LOCKING
	50102	MULTIPHASE MP35N PASSIVATED	
	50124	PLATING CADMIUM	
77194	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
77330-820	10267	CRES A286 FASTENER MATL ONLY	
	06247	LUBE DRY MOS2/SILICATE	
78545-XXX-XX	10424	NI STA INCO 718 FASTENER ONLY	BOLT,TENSION
788056/57	05339	RUBBER BUTYL B612-70	SEAL
79R5309	10089	CRES 302 COND B BAR AND WIRE	
801-5	00019	NYLON PLASTIC	
8106	20198	ADHES EC1357 NEOPRENE CEMENT	
	10391	CRES 302/304/316 SHT PLT WIRE	
	30082	PLATING CADMIUM & CHROMATE	
	05433	RUBBER NEOPRENE	
	10358	STEEL SAE/AISI 1008-1010	
	30143	ZINC & ZINC PLATING	
813-12	30121	CRES 17-4PH COND A	PUNCH

MSFC-HDBK-527 REV F 9999942 0006997 6

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
813-27-3	10377	AL 5056 WIRE SCREEN	SCREEN
818X5XXTE	10370	CRES 316 COND A & B BAR	
	00515	GREASE PERFLUORINATED	
	05278	RUBBER ETHYLENE PROPYLENE	
	00016	TEFLON TFE	
818X5XXTE2	10370	CRES 316 COND A & B BAR	
	00515	GREASE PERFLUORINATED	
	05395	RUBBER AF-E-411 EPDR	
	00016	TEFLON TFE	
818X5XXTT	10370	CRES 316 COND A & B BAR	
	00515	GREASE PERFLUORINATED	
	00016	TEFLON TFE	
87CX	10046	PLATING NI ELECTROLESS	
	10513	STEEL 4XXX/8XXX OVER 220KSI	
8A04S1A04FXXXX	10098	CRES 321 ANN BAR SHP FRG WIRE	
8X6HX6-SS	10370	CRES 316 COND A & B BAR	
9-761-X	10318	CRES 304L/316L WIRE/SCRN/CLOTH	
92944	10268	CRES 300 SERIES FASTENER MATL	
	10506	CRES 303/304 BAR AND WIRE	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
	05519	RUBBER E2024/2041/2038 SILICON	
92944/92947	05519	RUBBER E2024/2041/2038 SILICON	
92945	10268	CRES 300 SERIES FASTENER MATL	
	10506	CRES 303/304 BAR AND WIRE	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
	05519	RUBBER E2024/2041/2038 SILICON	
92946	10268	CRES 300 SERIES FASTENER MATL	
	10506	CRES 303/304 BAR AND WIRE	
	10090	CRES 304 ANN SHT PLT STRIP	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
92947	10268	CRES 300 SERIES FASTENER MATL	
	10506	CRES 303/304 BAR AND WIRE	
	10090	CRES 304 ANN SHT PLT STRIP	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
97-110-SN	10638	BE-CU ALLOY STRIP	
	10445	PLATING TIN	
97-555	10638	BE-CU ALLOY STRIP	SHIELDING

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
A-79-32-2	10321	BRASS, ALL FORMS	
	10281	PLATING SILVER, FASTENERS ONLY	
	05148	RUBBER 950-C-1569 SIL-GRADE 50	
	10256	SPRING BE-CU COND A WIRE	
	00016	TEFLON TFE	
A02636	10146	SPRING ELGILOY RC 55 WIRE STP	
	00016	TEFLON TFE	
A1128	99011	SEE FILE FOR MATERIALS	
A1155	99011	SEE FILE FOR MATERIALS	
A22	60082	POLYESTER	SHOULDER WASHER
A3122-10-1	05559	COATING PHOSPHATE (INORGANIC)	
	20440	CTNG PHENOLIC BASE	
	10515	STEEL 1055/1090 LOW CARBON	
A43-AP-17SN 046	10292	AL 2024-T6 BAR, ROD & WIRE	
	10638	BE-CU ALLOY STRIP	
	10277	COATING ANODIC - TYPE 2	
	10268	CRES 300 SERIES FASTENER MATL	
	20132	CTNG BLACK OXIDE	
	00070	MOLD CPD FS10 DAP	
	10328	PLATING GOLD	
	10046	PLATING NI ELECTROLESS	
	02976	RUBBER SILICONE	
	10256	SPRING BE-CU COND A WIRE	
AA1535-XX-XX	10370	CRES 316 COND A & B BAR	
AA670XX-XXKX	10370	CRES 316 COND A & B BAR	
AD 4W3	10335	AL 2117-T4 ANN ROD&WIRE RIVET	BLIND RIVET
	10276	COATING ANODIC	
AD152-0016	02343	LAMIN PAPER/PHENOLIC	
AE5170100	10510	CRES 304	BRAZE FITTING
	50137	WELD WIRE NI-CU BASE	
AE5170200	10268	CRES 300 SERIES	JOINT
AE5170300	10413	CRES 304L	ELBOW
AE5171104	10268	CRES 300 SERIES	UNION
AE5171200	10431	CRES 300 SERIES	BRAZE FITTING
AE5171300	10268	CRES 300 SERIES	UNION
AE5173003	10413	CRES 304L	UNION

MSFC-HDBK-527 REV F ■ 9999942 0006999 T ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AGS-2045	10335	AL 2117-T4	RIVET
AGS-2046	10335	AL 2117-T4	RIVET
AGS-2068	10335	AL 2117-T4	RIVET
AM155205	10515	STEEL 1055-1090 LOW CARBON	
AN 819-4J	10413	CRES 304	SLEEVE
AN 824-4D	10003 10277	AL 6061/T6 ANODIC CTNG T2	TEE
AN10-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN10CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN11-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN11CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN12-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN123451	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123452	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123453	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123454	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123455	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123456	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123457	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123458	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123459	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123460	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123461	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123462	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123463	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123464	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123465	10135	NI INCONEL 600 BAR	RIVET, SOLID

MSFC-HDBK-527 REV F ■ 9999942 0007000 0 ■

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN123466	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123467	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123468	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123469	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123470	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123471	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123472	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123473	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123474	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123475	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123476	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123477	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123478	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123479	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123480	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123481	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123482	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123483	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123484	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123485	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123486	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123487	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123488	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123489	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123490	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123491	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123492	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123493	10135	NI INCONEL 600 BAR	RIVET, SOLID

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN123494	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123495	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123496	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123497	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123498	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123499	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123500	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123501	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123502	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123503	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123504	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123505	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123506	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123507	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123508	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123509	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123510	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123511	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123512	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123513	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123514	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123515	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123516	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123517	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123518	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123519	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123520	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123521	10135	NI INCONEL 600 BAR	RIVET, SOLID

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN123522	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123523	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123524	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123525	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123526	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123527	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123528	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123529	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123530	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123531	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123532	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123533	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123534	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123535	10125	NI INCONEL 600 BAR	RIVET, SOLID
AN123536	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123537	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123538	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123539	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123540	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123541	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123542	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123543	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123544	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123545	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123546	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123547	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123548	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123549	10135	NI INCONEL 600 BAR	RIVET, SOLID

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN123550	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123551	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123552	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123553	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123554	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123555	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123556	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123557	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123558	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123559	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123560	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123561	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123562	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123563	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123564	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123565	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123566	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123567	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123568	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123569	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123570	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123571	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123572	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123573	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123574	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123575	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123576	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123577	10135	NI INCONEL 600 BAR	RIVET, SOLID

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN123578	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123579	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123580	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123581	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123582	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123583	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123584	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123585	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123586	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123587	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123588	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123589	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123590	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123591	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123592	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123593	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123594	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123595	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123596	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123597	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123598	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123599	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN123600	10135	NI INCONEL 600 BAR	RIVET, SOLID
AN124951	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124952	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124953	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124954	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124955	10675	RIVET CRES 18-8	RIVET, 100 CRSK

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN124956	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124957	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124958	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124959	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124960	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124961	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124962	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124963	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124964	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124965	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124966	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124967	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124968	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124969	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124970	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124971	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124972	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124973	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124974	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124975	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124976	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124977	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124978	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124979	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124980	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124981	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124982	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124983	10675	RIVET CRES 18-8	RIVET, 100 CRSK

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0007006 1

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN124984	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124985	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124986	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124987	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124988	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124989	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124990	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124991	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124992	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124993	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124994	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124995	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124996	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124997	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124998	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN124999	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125000	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125001	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125002	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125003	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125004	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125005	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125006	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125007	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125008	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125009	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125010	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125011	10675	RIVET CRES 18-8	RIVET, 100 CRSK

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN125012	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125013	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125014	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125015	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125016	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125017	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125018	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125019	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125020	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125021	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125022	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125023	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125024	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125025	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125026	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125027	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125028	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125029	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125030	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125031	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125032	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125033	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125034	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125035	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125036	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125037	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125038	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125039	10675	RIVET CRES 18-8	RIVET, 100 CRSK

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN125040	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125041	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125042	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125043	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125044	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125045	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125046	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125047	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125048	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125049	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125050	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125051	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125052	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125053	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125054	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125055	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125056	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125057	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125058	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125059	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125060	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125061	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125062	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125063	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125064	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125065	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125066	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125067	10675	RIVET CRES 18-8	RIVET, 100 CRSK

MSFC-HDBK-527 REV F ■ 9999942 0007009 7 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN125068	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125069	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125070	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125071	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125072	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125073	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125074	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125075	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125076	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125077	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125078	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125079	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125080	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125081	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125082	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125083	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125084	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125085	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125086	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125087	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125088	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125089	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125090	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125091	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125092	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125093	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125094	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125095	10675	RIVET CRES 18-8	RIVET, 100 CRSK

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN125096	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125097	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125098	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125099	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125100	10675	RIVET CRES 18-8	RIVET, 100 CRSK
AN125401	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125402	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125403	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125404	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125405	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125406	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125407	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125408	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125409	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125410	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125411	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125412	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125413	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125414	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125415	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125416	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125417	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125418	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125419	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125420	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125421	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125422	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125423	10675	RIVET CRES 18-8	RIVET, UNIV HEAD

MSFC-HDBK-527 REV F 9999942 0007011 5

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN125424	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125425	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125426	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125427	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125428	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125429	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125430	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125431	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125432	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125433	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125434	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125435	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125436	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125437	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125438	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125439	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125440	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125441	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125442	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125443	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125444	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125445	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125446	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125447	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125448	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125449	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125450	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125451	10675	RIVET CRES 18-8	RIVET, UNIV HEAD

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN125452	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125453	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125454	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125455	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125456	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125457	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125458	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125459	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125460	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125461	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125462	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125463	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125464	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125465	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125466	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125467	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125468	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125469	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125470	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125471	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125472	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125473	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125474	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125475	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125476	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125477	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125478	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125479	10675	RIVET CRES 18-8	RIVET, UNIV HEAD

MSFC-HDBK-527 REV F 9999942 0007013 9

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN125480	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125481	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125482	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125483	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125484	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125485	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125486	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125487	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125488	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125489	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125490	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125491	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125492	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125493	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125494	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125495	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125496	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125497	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125498	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125499	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125500	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125501	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125502	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125503	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125504	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125505	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125506	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125507	10675	RIVET CRES 18-8	RIVET, UNIV HEAD

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN125508	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125509	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125510	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125511	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125512	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125513	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125514	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125515	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125516	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125517	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125518	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125519	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125520	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125521	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125522	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125523	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125524	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125525	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125526	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125527	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125528	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125529	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125530	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125531	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125532	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125533	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125534	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125535	10675	RIVET CRES 18-8	RIVET, UNIV HEAD

MSFC-HDBK-527 REV F 9999942 0007015 2

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN125536	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125537	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125538	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125539	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125540	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125541	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125542	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125543	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125544	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125545	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125546	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125547	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125548	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125549	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN125550	10675	RIVET CRES 18-8	RIVET, UNIV HEAD
AN12CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN13-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN13CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN14-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN14CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN15-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN15CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN16-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN16CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN17-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE

MSFC-HDBK-527 REV F 9999942 0007016 4

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN17CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN18-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN18CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN19-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN19CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN20-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN20CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN3-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN310CXX	30075	CRES 416 BAR FREE MACHINING	NUT, PLAIN
AN315CXX	30075	CRES 416 BAR FREE MACHINING	NUT, HEX
AN316CXX	10268	CRES 300 SERIES FASTENER MATL	NUT, HEX
AN320-XX	30082 10358	PLATING CADMIUM & CHROMATE STEEL SAE 1010	NUT, PLAIN
AN320CXX	10268	CRES 300 SERIES FASTENER MATL	NUT, PLAIN
AN3CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN4-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN416-X	30082 30142	PLATING CADMIUM & CHROMATE STEEL 1095 (SPRING)	PIN, RETAINING
AN42-CX	30120	CRES 431 BAR SHP FRG	BOLT, EYE
AN43-CX	30120	CRES 431 BAR SHP FRG	BOLT, EYE
AN44-CX	30120	CRES 431 BAR SHP FRG	BOLT, EYE
AN45-CX	30120	CRES 431 BAR SHP FRG	BOLT, EYE
AN46-CX	30120	CRES 431 BAR SHP FRG	BOLT, EYE
AN47-CX	30120	CRES 431 BAR SHP FRG	BOLT, EYE
AN48-CX	30120	CRES 431 BAR SHP FRG	BOLT, EYE
AN49-CX	30120	CRES 431 BAR SHP FRG	BOLT, EYE

MSFC-HDBK-527 REV F 9999942 0007017 6

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN4CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN5-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN500-XX-XX	30082 10358	PLATING CADMIUM & CHROMATE STEEL SAE 1010	SCREW, MACHINE
AN500DXX-XX	10268	CRES 300 SERIES FASTENER MATL	SCREW, MACHINE
AN501ADXX-XX	10268	CRES 300 SERIES FASTENER MATL	SCREW, MACHINE
AN505CXX-XX	10606	CRES 18-8 BAR	SCREW, MACHINE
AN515CXX-XX	10606	CRES 18-8 BAR	SCREW, MACHINE
AN535-XX-XX	30082 10359	PLATING CADMIUM & CHROMATE STEEL AISI/SAE 1010 TO 1040	SCREW, DRIVE
AN565AXXXXHXX	30082 10513	PRATING CADMIUM & CHROMATE STEEL 4XXX/8XXX ABOVE 220 KSI	SETSCREW
AN565XCXXXX	30080	CRES 303 FREE MACHINING	SETSCREW
AN5CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN6-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN6227-XX	05499	RUBBER NITRILE	PACKING, "O"RING
AN6230-XX	05499	RUBBER NITRILE	GASKET, "O"RING
AN6289DXX	30105 10277	AL 2014-T6,2024-T6/T851 BAR COATING ANODIC - TYPE 2	NUT, TUBE
AN6289JXX	10351	CRES 304 ANN BAR SHP FRG WIRE	NUT, TUBE
AN6CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN7-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN735DXX	10408	AL 2024T3/T4X/T6X/T8X CLD SHT	CLAMP, LOOP
AN737TWXX	10268 30149	300 CRES 400 CRES	HOSE CLAMP
AN737XXXXX	10268	CRES 300 SERIES FASTENER MATL	CLAMP, HOSE
AN742DXX	10408	AL 2024T3/T4X/T6X/T8X CLD SHT	CLAMP, LOOP
AN742F38	10289	321/347 CRES	CLAMP LOOP
AN742HXX	10289	CRES 321/347 ANN SHT STD ONLY	CLAMP, LOOP

MSFC-HDBK-527 REV F 9999942 0007018 8

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN743-XX	30111 10277	AL 2024-T3/T4 SHEET COATING ANODIC - TYPE 2	BRACKET, CLAMP
AN743BZ	10408	AL 2024-0 CLAD PLATE SHEET	BRACKET,SUPPORT CLAMP
AN743C-10	50365	CRES 302 ANN THRU 1/2 HD STRIP	BRACKET,SUPPORT CLAMP
AN7CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN8-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN804JXX	10351	CRES 304 ANN BAR SHP FRG WIRE	TEE, TUBE
AN806-JXX	10351	CRES 304 ANN BAR SHP FRG WIRE	PLUG, TUBE
AN806-KXX	10370	CRES 316 COND A & B BAR	PLUG, TUBE
AN806-SXX	10100	CRES 347 ANN BAR SHP FRG WIRE	PLUG, TUBE
AN814-XK	10370	CRES 316	PLUG & BLEEDER
AN814-XS	10390	CRES 347	PLUG&BLEEDER
AN814-XXD	30105 10277	AL 2014-T6, 2024-T6/T851 BAR COATING ANODIC - TYPE 2	PLUG & BLEEDER
AN814-XXJ	10351	CRES 304 ANN BAR SHP FRG WIRE	PLUG & BLEEDER
AN815-XXJ	10351	CRES 304 ANN BAR SHP FRG WIRE	UNION, TUBE
AN815-XXS	10100	CRES 347 ANN BAR SHP FRG WIRE	UNION, TUBE
AN816-XD	10003 10277	AL2024-T851/T6/T62 ANODIC CTNG T2	ADAPTER
AN816-XXK	10370	CRES 316 COND A & B BAR	ADAPTER, PIPE
AN818-XXD	30105 10277	AL 2014-T6, 2024-T6/T851 BAR COATING ANODIC - TYPE 2	NUT, TUBE
AN818-XXJ	10351	CRES 304 ANN BAR SHP FRG WIRE	NUT, TUBE
AN818-XXK	10370	CRES 316 COND A & B BAR	NUT, TUBE
AN832-XXS	10100	CRES 347 ANN BAR SHP FRG WIRE	UNION, TUBE
AN833-XXJ	10351	CRES 304 ANN BAR SHP FRG WIRE	ELBOW, TUBE
AN8CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AN9-X	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	BOLT, MACHINE
AN910-XXJ	10351	CRES 304 ANN BAR SHP FRG WIRE	COUPLING, PIPE

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AN911-XXK	10370	CRES 316 COND A & B BAR	NIPPLE, PIPE
AN912-XXJ	10351	CRES 304 ANN BAR SHP FRG WIRE	BUSHING, PIPE
AN918-XXJ	10351	CRES 304 ANN BAR SHP FRG WIRE	CROSS, PIPE
AN919-XXS	10100	CRES 347 ANN BAR SHP FRG WIRE	REDUCER, TUBE
AN924-XXJ	10315	CRES 302/304/316 FASTNRS ONLY	NUT, TUBE
AN924-XXK	10370	CRES 316 COND A & B BAR	NUT, TUBE
AN924-XXS	10100	CRES 347 ANN BAR SHP FRG WIRE	NUT, TUBE
AN929-XX	30105 10277	AL 2014-T6 CTNG ANODIC TY2	CAP ASSEMBLY
AN929-XXJ	10351	CRES 304 ANN BAR SHP FRG WIRE	CAP ASSEMBLY
AN935-XXXX	30082 10515	PLATING CADMIUM & CHROMATE STEEL 1055-1090 LOW CARBON	WASHER, LOCK
AN938JXX	10351	CRES 304 ANN BAR SHP FRG WIRE	TEE, TUBE
AN939JXX	10351	CRES 304 ANN BAR SHP FRG WIRE	ELBOW, TUBE
AN960-XXXX	30082 10358	PLATING CADMIUM & CHROMATE STEEL SAE 1010	WASHER, FLAT
AN960CXL	10431	CRES 300 SERIES NON-FREE MACH	WASHER
AN960CXXXX	21132 10268	COATING BLACK OXIDE CRES 300 SERIES FASTENER MATL	WASHER, FLAT
AN960DXL	50256	AL 2024-T3 CLAD SHEET & PLATE	WASHER
AN960DXXXX	10502 10277	AL 1100/3003/2024-T3 CLD SHT COATING ANODIC - TYPE 2	WASHER, FLAT
AN960PDXXXX	10502 10277 00666	AL 1100/3003/2024-T3 CLD SHT COATING ANODIC - TYPE 2 CTNG CONVERSION CHROMATE INORG	WASHER, FLAT
AN9CX	30120	CRES 431 BAR SHP FRG	BOLT, MACHINE
AP244JXX	10351	CRES 304 ANN BAR SHP FRG WIRE	
AP2686J	10351	CRES 304 ANN BAR SHP FRG WIRE	
AP309P	10430	CRES 17-4PH H1075 BAR(RES 266)	
AP391P	10430	CRES 17-4PH H1075 BAR(RES 266)	
AP525	10430	CRES 17-4PH H1075 BAR(RES 266)	

MSFC-HDBK-527 REV F 9999942 0007020 6

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
AP526	10430	CRES 17-4PH H1075 BAR(RES 266)	
AR10XXX-XXP1Q	10220	CRES 304 ANN WIRE	OMNISEAL
	20219	TEFLON/GLASS/MOS2	
AR10XXX-XXXA1H	30077	CRES 17-7PH RH9XX/10XX/TH10XX	OMNISEAL
	00016	TEFLON TFE	
AR10XXX-XXXA1Q	10220	CRES 304 ANN WIRE	OMNISEAL
	00016	TEFLON TFE	
AR10XXX-XXXG1Q	10220	CRES 304 ANN WIRE	OMNISEAL
	05736	TEFLON TFE/15% GRAPHITE	
AR138	10431	CRES 300 SERIES NON-FREE MACH	
AR2770	10431	CRES 300 SERIES NON-FREE MACH	
AS1038KXXXX	10370	CRES 316 COND A & B BAR	ELBOW, 90 DEG
ATEC-14	10321	BRASS, ALL FORMS	
	10322	BRONZE PHOSPHOR ALL FORMS	
	10370	CRES 316 COND A & B BAR	
	00339	LEXAN CLEAR POLYCARBON	
	10275	PLATING CHROMIUM (CLASS 2)	
B-05	10321	BRASS	LUG SOLDER
BB365-XX-XX	10267	CRES A286 FASTENER MATL ONLY	BOLT, BLIND
BC 1000	10716	BE-CU	PCB-GUIDE
BE-1218-5H-8	10406	INCONEL 718	BOLT
BHDR-()M-2	10399	CRES 17-4PH H1025 BAR FRG RING	
	00597	LUBE DRY	
	10275	PLATING CHROMIUM (CLASS 2)	
	10107	STEEL 52100 RC 55 BAR	
BLC5LA26S	30099	AL 2017 ALL TEMPERS	
	10292	AL 2024-T6 BAR ROD & WIRE	
	10613	AL 360F CAST	
	10276	COATING ANODIC TYPE 1	
	10277	COATING ANODIC TYPE 2	
	10399	CRES 17-4PH H1025 BAR FRG RING	
	30124	CRES 17-4PH H900/15-7MO TH1050	
	10516	CRES 17-7PH CH900 WIRE	
	10506	CRES 303/304 BAR AND WIRE	
	30002	CRES 440A,440B,440C BAR	
	00666	CTNG CONVERSION CHROMATE INORG	
	10148	SPRING 302 COND B WIRE	
	30087	STEEL 8735 SHEET (MS19069)	
BN372-XX	10267	CRES A286 FASTENER MATL ONLY	NUT, BLIND

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
BS10379-K1105	10321	BRASS, ALL FORMS	
	10046	PLATING NI ELECTROLESS	
BS10379-K1625	10321	BRASS, ALL FORMS	
	10275	PLATING CHROMIUM (CLASS 2)	
BS10412	10321	BRASS, ALL FORMS	
	10308	PLATING NICKEL ELECTRODEPOSIT	
BS18303	10321	BRASS, ALL FORMS	
	10308	PLATING NICKET ELECTRODEPOSIT	
BS40-XXX	30079	STEEL AISI 6150 (RC 46-50)	
BTXXLX-A	10267	CRES A286 FASTENER MATL ONLY	ESNA Z1200J
	10281	PLATING SILVER,FASTENERS ONLY	
BWR-600	10333	CU SHT PLT BAR ANN	
BXXXX-XXX	10515	STEEL 1055-1090 LOW CARBON	
BXXXX-XXXS	10262	CRES 302 HARD SHT PLT STP	
C3132-10-1	20440	CTNG PHENOLIC BASE	
	05559	CTNG PHOSPHATE (INORGANIC)	
	10515	STEEL 1055-1090 LOW CARBON	
C557-70-XXX	05516	RUBBER C557-70 CHLOROPRENE	
CA17014T	10267	CRES A286 FASTENER MATL ONLY	RECEPTACLE ASSY
CA17083-XXHS	10267	CRES A286 FASTENER MATL ONLY	STUD NUT
CA17104T	10407	NI INCO 718 1750 ST SHT & PLT	RETAINING RING
CA1711	10315	CRES 302/304/316 FASTENR ONLY	RECEPTACLE
CA1727	30077	CRES 17-7PH RH9XX/10XX/TH10XX	RETAINING RING
CA1733-X	10315	CRES 302/304/316 FASTENR ONLY	STUD NUT
CA20000T-2	10267	CRES A286 FASTENER MATL ONLY	
CA20000T-2B	10267	CRES A286 FASTENER MATL ONLY	
	10452	NI INCO 718 CASTING 1900 ST	
CA20001	10146	SPRING ELGILOY RC 55 WIRE STP	
CA20002	10088	CRES 301 ANN THRU 1/2 HD PT SH	
	10267	CRES A286 FASTENER MATL ONLY	
	00880	LUBE DRY ELECTROFILM 2306 INOR	
	10281	PLATING SILVER,FASTENERS ONLY	
	10146	SPRING ELGILOY RC 55 WIRE STP	
CA2010	30080	CRES 303 FREE MACHINING	
	10267	CRES A286 FASTENER MATL ONLY	

MSFC-HDBK-527 REV F 9999942 0007022 T

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
CA2035	10146	SPRING ELGILOY RC 55 WIRE STP	
CA2096T-X	10267	CRES A286 FASTENER MATL ONLY	
CA2097	10315	CRES 302/304/316 FASTENRS ONLY	
	10124	CRES A286 140 KSI SHEET & PLT	
	10267	CRES A286 FASTENER MATL ONLY	
	05072	LUBE DRY NA SILICATE BASE	
	10148	SPRING 302 COND B WIRE	
	10146	SPRING ELGILOY RC 55 WIRE STP	
CA2098	10315	CRES 302/304/316 FASTENRS ONLY	
CA2099	10088	CRES 301 ANN THRU 1/2 HD PT SH	
	10267	CRES A286 FASTENER MATL ONLY	
	05072	LUBE DRY NA SILICATE BASE	
	10281	PLATING SILVER,FASTENERS ONLY	
	10146	SPRING ELGILOY RC 55 WIRE STP	
CA440X-X	10399	CRES 17-4PH H1025 BAR FRG RING	
	10512	CRES 303/305 BAR	
	00019	NYLON PLASTIC	
CB-301-6	10270	MAGNET ALNICO V, VI, VIII	
CCLQ-XX	10268	CRES 300 SERIES FASTENR MATL	RIVET, BLIND
CCPQ-XX	10268	CRES 300 SERIES FASTENR MATL	
CD-12	60149	POLYETHYLENE	CAP
CEG-75C	10354	CU WIRE ELECTRICAL CONDUCTOR	
	05335	LAMIN GLASS/EPOXY	
CL-21-KA-XXX	10514	CRES CABLE 300 SERIES	
	10333	CU SHT PLT BAR ANN	
	00019	NYLON PLASTIC	
	10445	PLATING TIN	
CMS-115-0.XXX	10267	CRES A286 FASTENER MATL ONLY	
CMS-144-0.XXX	10267	CRES A286 FASTENER MATL ONLY	
CPA5150-1	30080	CRES 303 FREE MACHINING	
	05133	LEXAN 9600-116 POLYCARB	
CR 2162	10443	AL 5056	RIVET CHERRY LOCK
CR 2249	10443	AL 5056	RIVET
CR 2263	10443	AL 5056	RIVET, BLIND
CR 2539	10222	MONEL	RIVET CHERRY LOCK
	10135	NI INCO 600	

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
CR 2663	10443	AL 5056	RIVET CHERRY LOCK
CR117D-3	10443	AL 5056-O/H32 ROD & WIRE	
CS-696-41116	05205	TEFZEL ETFE	
CXXXX-XXX-XXXXM	10232	SPRING STEEL MUSIC WIRE	
CXXXX-XXX-XXXXS	10391	CRES 302/304/316 SHT PLT WIRE	
D 04	05369	MOLD CPD (DAP)	WASHER,SHOULDER
D 05	05369	MOLD CPD (DAP)	WASHER
D 20418	10346	CU ALLOY	SCREW LOCK
D 20420	10346	CU ALLOY	PAN HEAD SCREW
D-109-0101	05096	HALAR E-CTFE	
	00367	KYNAR HST PVF 2	
	10449	SOLDER 5SB	
	02151	TUBING TFE HST	
D-109-0102	05096	HALAR E-CTFE	
	00367	KYNAR HST PVF 2	
	10449	SOLDER 5SB	
	02151	TUBING TFE HST	
D-109-0103	05096	HALAR E-CTFE	
	00367	KYNAR HST PVF 2	
	10449	SOLDER 5SB	
	02151	TUBING TFE HST	
D-440-0101	10353	CU TUBE ANN NI PLATED SPLICE	
	05096	HALAR E-CTFE	
	02151	TUBING TFE HST	
D-440-0102	10353	CU TUBE ANN NI PLATED SPLICE	
	05096	HALAR E-CTFE	
	02151	TUBING TFE HST	
D-440-0103	10353	CU TUBE ANN NI PLATED SPLICE	
	05096	HALAR E-CTFE	
	02151	TUBING TFE HST	
D-440-0104	10353	CU TUBE ANN NI PLATED SPLICE	
	05096	HALAR E-CTFE	
	02151	TUBING TFE HST	
D-440-0105	10353	CU TUBE ANN NI PLATED SPLICE	
	05096	HALAR E-CTFE	
	02151	TUBING TFE HST	
D-440-0106	10353	CU TUBE ANN NI PLATED SPLICE	
	05096	HALAR E-CTFE	
	02151	TUBING TFE HST	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
D-440-0111	10353	CU TUBE ANN NI PLATED SPLICE	
	05096	HALAR E-CTFE	
	02151	TUBING TFE HST	
D-710-8.5 OA	10046	PLATING NI ELECTROLESS	
	10513	STEEL 4XXX/8XXX OVER 220 KSI	
D20419	10346	CU ALLOY	SCREW LOCK
D34019316	05056	LAMIN GL/EPOXY/CU	SUBSTRATE
D34019322	05056	LAMIN PLASTIC SHEET	SHIELD CARRIER
D34020898	10130	CRES SHIM STOCK	WASHER
D4S	10351	CRES 304 ANN BAR SHP FRG WIRE	
D5-XX	10506	CRES 303/304 BAR AND WIRE	
D562A-XX-XX	30112	AL 2024-T3/T4 PLATE BAR TUBE	
	10276	COATING ANODIC TYPE 1	
	10516	CRES 17-7PH CH900 WIRE	
	01455	RUBBER E515-8 EPR	
DBA51H-10-6P	10351	CRES 304 ANN BAR SHP FRG WIRE	
	05713	GLASS COMPRESSION (INORGANIC)	
	10131	MAGNETIC STL NI-FE ANN BAR	
	10328	PLATING GOLD	
	20077	RUBBER DEUTSCH 40S SILICONE	
DC-XX	60149	POLYETHYLENE	CAP, SHIPPING
DIN 1013	10413	CRES 304L	FITTING
DIN 125	10099	CRES 347	WASHER
DIN 125 A2.7	10390	CRES 321	WASHER
DIN 125 AE , A4	50092	AL CLAD 2024	WASHER
DIN 127	10087	CRES 301	SPRING WASHER
DIN 137	10087	CRES 301	WASHER , SPRING
DIN 1481	10268	CRES 300 SERIES	ROLL PIN
DIN 1783	50208	AL 5754	IDENT PLATE
DIN 1784	10217	AL 1100	STRAP , BONDING
DIN 2093	10087	CRES 301	SPRING CUP
DIN 2093-2	10139	NI INCO 750	SPRING
DIN 267 M3 +O M6	10097	CRES 321	SCREW , HEX-HEAD

MSFC-HDBK-527 REV F 9999942 0007025 5

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
DIN 267 AE OR A4	10279	AL 1200	SCREW , CHEESE
DIN 3017	10090	CRES 304	CLAMP
DIN 40621	20427	SLEEVING PVC	SLEEVE
DIN 41496	10321 10046 10649	BRASS NI PLATE TIODIZE ANODIC CTNG	LUG
DIN 433	10099	CRES 347	WASHER
DIN 439	50059	CRES 316L	NUT
DIN 46234	10638 10445	BE-CU ALLOY STRIP TIN PLATING	CABLE SOCKET
DIN 46435	10354 60435	CU WIRE LACKDRAHT 180HW11	WIRE DYNAMO
DIN 46438	10333 02151	CU TUBING TFE HST	BONDING STRAP
DIN 5401	10423	CRES 302	BALL BEARING
DIN 547	10097	CRES 321	NUT
DIN 553	10268	CRES 300 SERIES	PIN THREADED
DIN 553 A4	10268	CRES 300 SERIES	PIN , THREADED
DIN 612-A4	10268	CRES 300 SERIES	PAN HEAD SCREW
DIN 661	10217	AL 1100	RIVET
DIN 671	10095	CRES 316	SCREW PANHEAD
DIN 6799	10087	CRES 301	CIRCLIP
DIN 6912	10370	CRES 316	SCREW
DIN 7	10268	CRES 300 SERIES	PIN , CYLINDER
DIN 7964	10515	STEEL (1050-1090)	SCREW
DIN 7985	10069	TI 6AL 4V	SCREW
DIN 7993	10515 10699	STEEL 1050-1090 TOOL STEEL	RING SNAP
DIN 84	10069	TI 6AL 4V	SCREW
DIN 84 E	50085	CRES 304	SCREW
DIN 84-A2	10351	CRES 304	SCREW

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
DIN 85	00019	NYLON	SCREW
DIN 9021 A6.4	10097	CRES 321	WASHER
DIN 912	10268	CRES 300 SERIES	SCREW HEX-HEAD
DIN 913	10268	CRES 300 SERIES	PIN , THREADED
DIN 913 M	10069	TI 6AL 4V	SCREW
DIN 916 A2	10351	CRES 304	SCREW
DIN 917	10431	CRES 300	NUT, CAP
DIN 927	10268	CRES 300 SERIES	SCREW , TRUNION
DIN 933 A4	10370	CRES 316	SCREW , HEX-HEAD
DIN 933 A2	50085	CRES 304	SCREW , HEX-HEAD
DIN 934	10268	CRES 300 SERIES	NUT , HEX
DIN 934 M2	10069	TI 6AL 4V	NUT
DIN 936	10268	CRES 300 SERIES	NUT , HEX
DIN 963 A-4	10370	CRES 316	SCREW
DIN 963 A-2	50085	CRES 304	SCREW
DIN 963 M2	10069	TI 6AL 4V	SCREW
DIN 963 M3	10431	CRES 300 SERIES	SCREW
DIN 965	10321	BRASS ALL FORMS	SCREW
DIN 985	30130	STEEL LOW CARBON	NUT
DN58070-1	30080	CRES 303 FREE MACHINING	
	10090	CRES 304 ANN SHT PLT STRIP	
	10308	PLATING NICKEL ELECTRODEPOSIT	
	05343	RUBBER S604-70 SILICONE	
	10232	SPRING STEEL MUSIC WIRE	
DOLN 229	30055	AL 2024-T351	SPACER
	10276	ANODIC CTNG TYPE 1	
DOLN 230	10097	CRES 321	WASHER
DOLN 304	10097	CRES 321	WASHER
DOLN 507	10443	AL 5056	RIVET
DOLN 59	10124	CRES A286	WASHER

MSFC-HDBK-527 REV F 9999942 0007027 9

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
DOLN 94	10304	AL 5052	SLEEVE
DP-XX	60149	POLYETHYLENE	PLUG, SHIPPING
EA-06-062TJ-350	01342	FILM KAPTON POLYIMINE	
	10649	TIODIZE ANODIC COATING	
EGPX-C-XX-XPT	10024	AL 6061-T6/T6511 EXT BR SHP TB	
	10283	COATING ANODIC TYPE 3 (HARD)	
	10638	CRES 17-4PH H1075 FRGS TUBING	
	10268	CRES 300 SERIES FASTENER MATL	
	00597	LUBE DRY	
ENN 123	10217	AL 1100	LABEL
ENN 216	10348	AL 11XX ANN FOIL	SHEET
ENN 216 AX	10348	AL 11XX ANN FOIL	NAMEPLATE
	05173	TAPE 465 ACRYLIC FILM	
ENN 308	10097	CRES 321	PIN PARALLEL
ENN 364	10069	TI 6AL 4V	SCREW , CHEESE-HEAD
ENN 365	50055	AL 2024/T62	NUT , SELF-LOCKING
ENN 366	30108	AL 2024/T4	INSERT
	00666	CTNG CHROMATE	
ENN 367	50055	AL 2024/T62	NUT
ENN 370	50503	CRES 420	SPRING , RETAINING
ENN 370 F	50503	CRES 420F	RING
ENN 374	10069	TI 6AL 4V	SCREW , CHEESE
ENN 375	10011	CRES 302	SCREW , CAPTIVE
ENN 376	10069	TI 6AL 4V	SCREW
ENN 377	30108	AL 2024-T4	INSERT
	10279	CTNG ANODIC	
ENN 378	10348	AL/FOIL	PLATE , IDENTIFICATION
ENN 378F	10217	AL 1100	PLATE
ENN 379	10292	AL 2024-T6	INSERT
	50148	AL 6061-0	
	10276	CTNG ANODIC	
	00666	CTNG CONVERSION CHROMATE	
ENN 379 E	50055	AL 2024-T66	INSERT ASSEMBLY
	10325	AL 6061-0	
	00666	CONVERSION CHROMATE	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
ENN 379 E	10276	CTG,ANODIC-TY1	INSERT ASSEMBLY
ENN 382	10069	TI 6AL 4V	SCREW , CHEESE
ENN 404	10217	AL 1100	BONDING STRAP
ENN 407E	10279	AL 1100	BONDING STRIP
ENN 512-03	10475	CRES 305	SEAL
ENN 512-30	10475	CRES 305	SEAL
ENN 517	10217	AL 1100	TAPE , ID
ENN 803	10399	CRES 17-4PH H1025	RECEPTACLE
ENN 803-U	30111	AL 2024/T3	HANDLE
ENN 804-F	61744	SCOTCHCAL FOIL TY 8011	WARNING STREAMER
ENN-512-02B-2	05005	VITON-B	O-RING
EWB 0420	10267	CRES A286	BOLT
EWB 0420-XX-XX	10267	CRES A286 FASTENER MATL ONLY	BOLT, TENSION
EWBM 26-XX-XX	50102	MULTIPHASE MP35N 260 KSI	BOLT, TENSION
EWSBM 26-XX-XX	50102	MULTIPHASE MP35N 260 KSI	BOLT, SHEAR
EWSNM 26-XXXX	06172 50102 10281	LUBE DRY MOS2 MULTIPHASE MP35N 260 KSI PLATING SILVER, FASTENR ONLY	NUT, FLEXLOC
F-710NRL	10046 10232 10513	PLATING NI ELECTROLESS SPRING STEEL MUSIC WIRE STEEL 4XXX/8XXX OVER 220 KSI	
F12056	10267 10407 10281	CRES A286 FASTENER MATL ONLY NI INCO 718 1750 ST SHT PLT PLATING SILVER,FASTENER ONLY	
F391780/794	50055 10277	AL 2024-T6 CTG,ANODIC-TY2	WASHER METRIC
F392000/573	10401	TI 6AL 4V	BOLT
F392574/783	10401	TI 6AL 4V	BOLT,ISO.SOCKET HEAD
F392964/993	10011	CRES A286	NUT ISOMETRIC
F393000/114	10011 05158	CRES A286 LUBRICANT,EVERLUBE 620	NUT SELF-LOCKING BI-HX
F3931795/809	10095	CRES 316	WASHER METRIC

MSFC-HDBK-527 REV F 9999942 0007029 2

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
F393537-202/1248	10335 10277	AL 2117 CTG,ANODIC-TY2	RIVET MUSHROOM HEAD
F393538-202/1248	10335 10277	AL 2117 CTG,ANODIC-TY2	RIVET 100 CS'K HEAD
F393541/960	10401	TI 6AL 4V	BOLT,ISO. CS'K HEAD
F393961-01/61	10011	CRES A286	HUCK FASTENER
F393987	30066	CRES 430	NUT BARREL
F393988/999	10011 05158	CRES A286 LUBRICANT,EVERLUBE 620	ANCHOR NUT
F393993	10267	CRES A286	NUT PLATE
F393998	10401	TI 6AL 4V	BOLT SHOULDERED
F393999/4001	10401	TI 6AL 4V	BOLT SHOULDERED
F394000/029	10257	AL-BRONZE	BUSHING FLANGED
F394002	10401	TI 6AL 4V	BOLT M18 SPECIAL
F394019	50055 10277	AL 2024-T6 SHT CTG, ANODIC-TY2	SHIM
F394020	50055 10277	AL 2024-T6 SHT CTG, ANODIC-TY2	SHIM
F394048	30066	CRES 430	BARREL NUT
F394050/1	50055 10277	AL 2024-T6 SHT CTG,ANODIC-TY2	STRESS PADS
F394056	10382 05158	CRES 302 LUBE DRY EVERLUBE 620	SPIROL PIN
F394056/64	10294 05158	CRES 302 LUBRICANT,EVERLUBE 620	PIN SPIROL
F394115-01/07	50055 10277	AL 2024-T6 SHT CTG,ANODIC-TY2	SHIM
F394116-01/07	50055 10277	AL 2024-T6 SHT CTG, ANODIC-TY2	SHIM
F394117-01/07	50055 10277	AL 2024-T6 SHT CTG, ANODIC-TY2	SHIM
F394268/9	50055 10277	AL 2024-T6 SHT CTG,ANODIC-TY2	STRESS PADS
F394302-01/07	50055 10277	AL 2024-T6 SHT CTG, ANODIC-TY2	SHIM

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
F394305-01/07	50055 10277	AL 2024-T6 SHT CTG, ANODIC-TY2	SHIM
F394306-01/07	50055 10277	AL 2024-T6 SHT CTG, ANODIC-TY2	SHIM
F394307-01/07	50055	AL 2024-T6 SHT CTG, ANODIC-TY2	SHIM
F394311-01/07	50055 10277	AL 2024-T6 SHT CTG, ANODIC-TY2	SHIM
F394340	50055	AL 2024-T6 SHT	PIN HEADED
F394394	50055 10277	AL 2024-T6 SHT CTG,ANODIC-TY2	STRESS PADS
F394446	10335 10277	AL 2117 CTG,ANODIC-TY2	RIVET
F394473	50055 10277	AL 2024-T6 SHT CTG,ANODIC-TY2	STRESS PADS
F394549-01/07	50055 10277	AL 2024-T6 SHT CTG, ANODIC-TY2	SHIM
F394551-01/07	50055 10277	AL 2024-T6 SHT CTG, ANODIC-TY2	SHIM
F394593	10401	TI 6AL 4V	BOLT BI-HEX HEAD
F394594	10011 05158	CRES A286 EVERLUBE 620	NUT-HEX
F394595	50055 10277	AL 2024-T6 SHT CTG,ANODIC-TY2	WASHER
F394599	10043 05633	AL 2024 BAR CTG,CONVERSION	WASHER,RECESSED
F394644	50055 10277	AL 2024-T6 SHT CTG,ANODIC-TY2	WASHER M18 SPECIAL
F394646	50092 10277	ALCLAD 2014 CTG,ANODIC-TY2	WASHER 3/4 UNF
F394649	30105 05633	AL 2014 BAR CTG,CONVERSION	WASHER M5 SPECIAL
F394743/752	06236 10401	CTG,CHEMGLAZE II A276 TI 6AL 4V	BOLT,ISO. SOCKET HEAD
F394844	50055	AL 2024-T6 SHT	WASHER M12
F394885	10011	CRES A286	NUT HOUSING

MSFC-HDBK-527 REV F 9999942 0007031 0

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
F394886	10011	CRES A286	SPACER
F394887-01/07	50055	AL 2024-T6 SHT	SHIM
	10277	CTG, ANODIC-TY2	
F394968	10069	TI 6AL 4V	BOLT
F394973	10275	PLATING CR	BALL END
	10054	TI 5AL 2.5 SN	
F394974-01/08	50056	AL 2024-T81	SHIM
	10277	CTG,ANODIC-TY2	
F395404/5	50055	AL 2024-T6 SHT	STRESS PADS
	10277	CTG,ANODIC-TY2	
F395406-1/7	50055	AL 2024-T6 SHT	SHIM
	10277	CTG,ANODIC-TY2	
F5031	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENER ONLY	
FA-8-8AEX	10046	PLATING NI ELECTROLESS	
	10513	STEEL 4XXX/8XXX OVER 220 KSI	
FC 3010	10382	CRES 302	HINGE
	10645	SPRING CRES 304	
FC 3020	10124	CRES A286	NUT , ANCHOR
	05158	LUBE DRY , EVERLUBE 620	
FC 3030	10148	CRES 302	STUD
	10148	CRES 302	
	10475	CRES 305	
	50364	ELGILOY	
FC 3041	10601	CRES 302	RECEPTACLE
FC 3071	10366	AL 1100	PLATE ID
FC 3072	10366	AL 1100	ID PLATE
FC 3080	10354	CU/BORON CU/AL	BONDING STRAP
	10445	PLATING TIN	
FC 3090	10389	CRES 15-5PH H1025	BOLT
	05158	LUBE DRY EVERLUBE 620 A	
FC 3110	30120	CRES 431	WASHER
FC 3120	50055	AL 2024	WASHER
	10046	NICKEL PLATED	
FC 3510	10022	AL 6061-T62	SEAL
	05339	RUBBER BUTYL B612-70	

MSFC-HDBK-527 REV F 9999942 0007032 2

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
FC 3520	10022	AL 6061-T62	SEAL
	05339	RUBBER BUTYL B612-70	
FC 3530	10399	CRES 17-4PH H1025	BEARING
	10106	CRES 440C	
FC 3540	10399	CRES 17-4PH H1025	BEARING
	10106	CRES 440C	
FC 3550	10399	CRES 17-4PH H1025	BEARING
	10106	CRES 440C	
FC 3560	30108	AL2024-T4	INSERT , FLOATING
	30080	CRES 303	
	50503	CRES 420 F	
	10039	PLATING SILVER	
FC 3570	10124	CRES A286	NUT , ANCHOR
	05158	LUBE DRY , EVERLUBE 620	
FC 3580	10011	CRES A286	BOLT , HI-HEX
FC 3591	10645	SPRING 304/CRES	SPRING
FC 3592	10645	SPRING 304/CRES	SPRING
FC 3670	10305	MULTIPHASE MP35N	BOLT
FC 3680	30120	CRES 431	WASHER
FC 3690	30120	CRES 431	WASHER
FC 3720	10276	ANODIC CTNG T1	BOLT
	05158	EVERLUBE 620	
	10069	TI 6AL 4V	
FC 3730	10645	SPRING 304 CRES	CIRCLIPS
FC 3760	10475	CRES 305	RECEPTACLE
FC 3780	30080	CRES 303	
FC 3790	10069	TI 6AL 4V	BOLT, CAPTIVE TENSION
	10649	TIODIZE ANODIC CTNG.	
FC 3810	00597	EVERLUBE 620	BOLT , TENSION
	10069	TI 6AL 4V	
FC 3910	10505	INCONNEL 718	BOLT , HEX-HEAD
FC 3920	10505	INCONEL 718	BOLT , TENSION
FC 3930	10505	INCONNEL 718	BOLT , TENSION
FC 3940	10505	INCONNEL 718	BOLT , TENSION

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
FC 3960	30120	CRES 431	BOLT , HEX-HEAD
	00597	EVERLUBE 620	
FC 3970	30120	CRES 431	BOLT
FC 3980	10505	NI INCO 718	BOLT , HEX-HEAD
FHL6010	30077	CRES 17-7PH RH9XX/10XX/TH10XX	
	10351	CRES 304 ANN BAR SHP FRG WIRE	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER, FASTENERS ONLY	
G/I-XXXXX	20037	ASBESTOS	
	10134	NI INCO 600 ANN SHT PLT STP	
G1107-XXH-M	30112	AL 2024-T3/T4 PLATE BAR TUBE	
	10023	AL 6061-T6/T651 BAR SHP ROD	
	10268	CRES 300 SERIES FASTENER MATL	
	10382	CRES 302 ANN BAR SHP FRG WIRE	
	10046	PLATING NI ELECTROLESS	
	05287	RUBBER NITRILE	
	00016	TEFLON TFE	
G1107-XXN-M	30112	AL 2024-T3/T4 PLATE BAR TUBE	
	10023	AL 6061-T6/T651 BAR SHP ROD	
	10046	PLATING NI ELECTROLESS	
	05287	RUBBER NITRILE	
G1109HXXM4-XS	30112	AL 2024-T3/T4 PLATE BAR TUBE	
	10023	AL 6061-T6/T651 BAR SHP ROD	
	10268	CRES 300 SERIES FASTENER MATL	
	10382	CRES 302 ANN BAR SHP FRG WIRE	
	10046	PLATING NI ELECTROLESS	
	05489	RUBBER DC 651 SILICONE	
	00016	TEFLON TFE	
G1109NXXM	30112	AL 2024-T3/T4 PLATE BAR TURE	
	10023	AL 6061-T6/651 BAR SHP ROD	
	10046	PLATING NI ELECTROLESS	
	05489	RUBBER DC 651 SILICONE	
G1136-XXM	10525	AL 2024/6061/A280 ALLOY	
	10431	CRES 300 SERIES NON-FREE MACH	
	10046	PLATING NI ELECTROLESS	
	05343	RUBBER S604-70 SILICONE	
G1422CXXM	10525	AL 2024/6061/A380 ALLOY	
	10431	CRES 300 SERIES NON-FREE MACH	
	10046	PLATING NI ELECTROLESS	
	05343	RUBBER S604-70 SILICONE	
G2469HXMX-2	30112	AL 2024-T3/T4 PLATE BAR TUBE	
	10023	AL 6061-T6/651 BAR SHP ROD	
	10268	CRES 300 SERIES FASTENER MATL	
	10382	CRES 302 ANN BAR SHP FRG WIRE	
	10046	PLATING NI ELECTROLESS	

MSFC-HDBK-527 REV F 9999942 0007034 6

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
G2469HXMX-2	05489	RUBBER DC 651 SILICONE	
	00016	TEFLON TFE	
G2469NXM	30112	AL 2024-T3/T4 PLATE BAR TUBE	
	10023	AL 6061-T6/651 BAR SHP ROD	
	10046	PLATING NI ELECTROLESS	
	05489	RUBBER DC 651 SILICONE	
G2470A-14R	10292	AL 2024-T6 BAR ROD WIRE	
	10023	AL 6061-T6/651 BAR SHP ROD	
	10507	AL 6061/6262-0/T6/T9 BAR	
	10277	COATING ANODIC - TYPE 2	
	10431	CRES 300 SERIES NON-FREE MACH	
	05344	RUBBER SILICONE	
G2684-XX	30112	AL 2024-T3/T4 PLATE BAR TUBE	
	10023	AL 6061-T6/651 BAR SHP ROD	
	10046	PLATING NI ELECTROLESS	
	05558	RUBBER CHO-SEAL 1217AG/FLURSIL	
	05557	RUBBER CHO-SEAL 1221AG/FLURSIL	
G311P405-XX-X-XX	10271	BERYLLIUM COPPER	CONNECTOR
	50170	BERYLLIUM COPPER	
	10321	BRASS	
	10634	COPPER LEADED NICKEL 7021	
G51T-A	60069	TEFLON (PTFE	GROMMET
G60-11-2523-1661	05351	BERYLLIA	WASHER
G60-11-4305-1663	05352	ALUMINA	WASHER
G62110-XX	10024	AL 6061-T6/T6511 BAR SHP TUBE	
	10046	PLATING NI ELECTROLESS	
	05344	RUBBER SILICONE	
G62707	10431	CRES 300 SERIES NON-FREE MACH	
G7143	10508	AL 2024-T851/T8511 BAR	
	10023	AL 6061-T6/651 BAR SHP ROD	
	10268	CRES 300 SERIES FASTENER MATL	
	10328	PLATING GOLD	
	10046	PLATING NI ELECTROLESS	
	10149	SPRING BE-CU AT WIRE & STRIP	
	00016	TEFLON TFE	
G8062-XXM	30112	AL 2024-T3/T4 PLATE BAR TUBE	
	10019	AL 6061-T4/451 BAR ROD SHAPE	
	10046	PLATING NI ELECTROLESS	
G8261N-8R	10023	AL 6061-T6/651 BAR SHP ROD	
	10277	COATING ANODIC - TYPE 2	
	10431	CRES 300 SERIES NON-FREE MACH	
	02976	RUBBER SILICONE	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
GF511P	10267	CRES A286 FASTENER MATL ONLY	
	00881	LUBE DRY EVERLUBE 812 (INORG)	
GPN 300	20427	SLEEVING PVC	CAP PROTECTION
GPN 610	60137	PVC	PROTECTION CAP
GSCXXXXNP	10483	CU SEAMLESS TUBING	RING, SHIELD
	10274	PLATING NICKEL/TIN	
H 4030	05776	BORON NITRIDE	INSULATING WASHER
H15XX-2E-XX	10047	AL 7075-T73XX RLD/DWN BAR ROD	PIN,SWAGE LOCKNG
	60059	CETYL ALCOHOL FASTENR LUBE	
	10277	COATING ANODIC - TYPE 2	
H238T1-XXX	10370	CRES 316 COND A & B BAR	
	06200	RUBBER B591-80 BUTYL	
	10148	SPRING 302 COND B WIRE	
H4 XXX	05776	BORON NITRIDE	WAFERS
H42-XX	10267	CRES A286 FASTENER MATL ONLY	
	00597	LUBE DRY	
HAQ12-X-100	05658	VELCRO HAQ12-2-200 NOMEX PILE	
HB 25 SE	50240	AL 5556	P-CLAMP
	05098	CLAMP CUSHION/SILICONE	
HB 28 SE	50240	AL 5556	P-CLAMP
	05098	CLAMP CUSHION/SILICONE	
HGW 2372	05543	LAMIN GLASS EPOXY	PCB
HL 10	10069	TI 6AL 4V	PIN
HL 112VF-X	10069	TI 6AL 4V	RIVET,HI LOK
HL 113VF-X	10069	TI 6AL 4V	RIVET,HI LOK CSK
HL 12VF-X	10069	TI 6AL 4V	RIVET,HI LOK
HL 13VF-X	10069	TI 6AL 4V	RIVET,HI LOK CSK
HL 18	50127	STEEL 4340	PIN (HI-LOK)
HL 70	10292	AL 2024-T6	COLLAR (HI-LOK)
	10277	CTNG ANODIC-T2	
HL 75K-XAWU	10124	CRES A286	COLLAR
HL11V TA-XX	10069	TI 6AL 4V	PIN
[illegible]-XXAWI	05168	CETYL ALCOHOL 96 PERCENT	HI-LOK
	10267	CRES A286 FASTENER MATL ONLY	

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0007036 T

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
HL185-XXAWI	10281	PLATING SILVER,FASTENERS ONLY	HI-LOK
HL240	10267	CRES A286 FASTENER MATL ONLY	HI-LOK PIN
HL278	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENER ONLY	
HL28	10336	CRES 305 ANN BAR	HI-LOK PIN
HL297-XXA	05168	CETYL ALCOHOL 96 PERCENT	HI-LOK COLLAR
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
HL297-XXKA	10267	CRES A286 FASTENER MATL ONLY	HI-LOK COLLAR
	00098	LUBE DRY 905 (INORGANIC)	
HL34-XX-XX-XX	60059	CETYL ALCOHOL FASTENR LUB ONLY	HI-LOK PIN
	30120	CRES 431 BAR SHP FRG	
HL3486PB-XX-XX-XX	60059	CETYL ALCOHOL FASTENR LUB ONLY	HI-LOK PIN ASSY
	10268	CRES 300 SERIES FASTENER MATL	
	30120	CRES 431 BAR SHP FRG	
	30082	PLATING CADMIUM & CHROMATE	
HL40-XX-XX	05168	CETYL ALCOHOL 96 PERCENT	HI-LOK PIN
	10267	CRES A286 FASTENER MATL ONLY	
HL4097PB-XX-XX-XX	60059	CETYL ALCOHOL FASTENR LUB ONLY	HI-LOK PIN ASSY
	10262	CRES 302 HARD SHEET PLT STRIP	
	10267	CRES A286 FASTENER MATL ONLY	
	30082	PLATING CADMIUM & CHROMATE	
HL410V-X-X	05168	CETYL ALCOHOL 96 PERCENT	HI-LOK PIN
	10365	TI 6AL-4V-STA BAR & FORGINGS	
HL411V-X-X	05168	CETYL ALCOHOL 96 PERCENT	HI-LOK PIN
	10365	TI 6AL-4V-STA BAR & FORGINGS	
HL4197PB-XX-XX-XX	60059	CETYL ALCOHOL FASTENR LUB ONLY	HI-LOK PIN ASSY
	10262	CRES 302 HARD SHEET PLT STRIP	
	10267	CRES A286 FASTENER MATL ONLY	
	30082	PLATING CADMIUM & CHROMATE	
HL70-XX	10292	AL 2024-T6 BAR ROD & WIRE	HI-LOK COLLAR
	05168	CETYL ALCOHOL 96 PERCENT	
	10277	COATING ANODIC - TYPE 2	
HL748-XX	05168	CETYL ALCOHOL 96 PERCENT	HI-LOK PIN
	10267	CRES A286 FASTENER MATL ONLY	
HL78K-XX	10267	CRES A286 FASTENER MATL ONLY	HI-LOK PIN
	00098	LUBE DRY 905 (INORGANIC)	
HL97-XX	05168	CETYL ALCOHOL 96 PERCENT	HI-LOK COLLAR
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
HL97K-XX	10267	CRES A286 FASTENER MATL ONLY	HI-LOK COLLAR
	00098	LUBE DRY 905 (INORGANIC)	
HLDA79-M5	10268	CRES 300 SERIES	
HLT270	10292	AL 2024-T6 BAR ROD & WIRE	HI-LOK COLLAR
	05168	CETYL ALCOHOL 96 PERCENT	
	10277	COATING ANODIC - TYPE 2	
HLT634	05168	CETYL ALCOHOL 96 PERCENT	
	10365	TI 6AL-4V-STA BAR & FORGINGS	
HM 41	10267	CRES A286	NUT
	10281	SILVER PLATING	
HN3G-XX-2	05133	LEXAN 9600-116 POLYCARB	
HN3P-XX-X-2	05298	NYLON 6/6	
HN5G-XX	05133	LEXAN 9600-116 POLYCARB	GROMMET
HN5P-XX	05298	NYLON 616	PLUNGER
HP232A-XXX	30112	AL 2024-T3/T4 PLATE BAR TUBE	
	05005	RUBBER VITON FLUID RESISTANT	
	10148	SPRING 302 COND B WIRE	
HS 104	10135	NI INCO 600	COLLAR
HS 131	10139	NI INCO 750	PIN (HI-SHEAR)
HS 132	10139	NI INCO 750	PIN (HI-SHEAR)
HS 15	30111	AL 2024/T4	COLLAR (HI-LOK)
HS 47	50146	STEEL 4140	RIVET
HS 48	50146	STEEL 4140	RIVET
HSBG1XVSS	10416	CRES 17-4PH H1150 BAR ROD FORG	
	10275	PLATING CHROMIUM (CLASS 2)	
	10107	STEEL 52100 RC 55 BAR	
HSBG8VCR	10416	CRES 17-4PH H1150 BAR ROD FORG	
	30008	CRES 440C RC 58 BAR FRG	
HSP6-141	10011	CRES A286 140 KSI BAR FRG TBNG	
	05072	LUBE DRY NA SILICATE BASE INOR	
	10505	NI INCO 718 ST 1750 OR 1950 BR	
	10275	PLATING CHROMIUM (CLASS 2)	
HT-M-1011	10268	CRES 300 SERIES FASTENER MATL	
HT9100-XX-XX	10267	CRES A286 FASTENER MATL ONLY	BOLT, SHEAR

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
HU8-134M	10416	CRES 17-4PH H1150 BAR ROD FORG	
	30002	CRES 440A,440B,440C BAR	
	00597	LUBE DRY	
HUDL9VCR1	10416	CRES 17-4PH H1150 BAR ROD FORG	
	30008	CRES 440C RC 58 BAR FRG	
	00597	LUBE DRY	
HW 41	10518	CRES A286	NUT
	10039	SILVER PLT	
J-XXX-7-1F-GM	05471	SEAL J-114-7-1F-GM TFE/GL/MOS2	
	10428	SPRING 17-7PH CH900 WIRE	
JM44LC28-WD1XRP	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	05309	CLAMP CUSH GE24449/13407-JM-RP	
JM44LC28-WD2XRP	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	05309	CLAMP CUSH GE24449/13407-JM-RP	
JM44LC28-WD3XRP	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	05309	CLAMP CUSH GE24449/13407-JM-RP	
JM44LC28-WD4XRP	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	05309	CLAMP CUSH GE24449/13407-JM-RP	
JM44LC28-WD5XRP	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	05309	CLAMP CUSH GE24449/13407-JM-RP	
JM44LC28-WD6XRP	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	05309	CLAMP CUSH GE24449/13407-JM-RP	
JM44LC28-WDOXRP	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	05309	CLAMP CUSH GE24449/13407-JM-RP	
JM44LC28-WH0XRP	05309	CLAMP CUSH GE24449/13407-JM-RP	
	10097	CRES 321 ANN SHT PLT STRIP	
JM44LC28-WH1XRP	05309	CLAMP CUSH GE24449/13407-JM-RP	
	10097	CRES 321 ANN SHT PLT STRIP	
JM44LC28-WH2XRP	05309	CLAMP CUSH GE24449/13407-JM-RP	
	10097	CRES 321 ANN SHT PLT STRIP	
JM44LC28-WH3XRP	05309	CLAMP CUSH GE24449/13407-JM-RP	
	10097	CRES 321 ANN SHT PLT STRIP	
JM44LC28-WH4XRP	05309	CLAMP CUSH GE24449/13407-JM-RP	
	10097	CRES 321 ANN SHT PLT STRIP	
JM44LC28-WH5XRP	05309	CLAMP CUSH GE24449/13407-JM-RP	
	10097	CRES 321 ANN SHT PLT STRIP	
JM44LC28-WH6XRP	05309	CLAMP CUSH GE24449/13407-JM-RP	
	10097	CRES 321 ANN SHT PLT STRIP	

MSFC-HDBK-527 REV F 9999942 0007039 5

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
JM44LC41H-105RP	05309	CLAMP CUSH GE24449/13407-JM-RP	
	10097	CRES 321 ANN SHT PLT STRIP	
JM44LC46SH0XGT	10088	CRES 301 ANN THRU 1/2 HD PT SH	
	00016	TEFLON TFE	
JM44LN4H0XXRG	05478	CLAMP CUSH GE24449/13407-JM-RG	
	10097	CRES 321 ANN SHT PLT STRIP	
	00016	TEFLON TFE	
JM44MC4H2-206RP	05309	CLAMP CUSH GE24449/13407-JM-RP	
	10097	CRES 321 ANN SHT PLT STRIP	
JM44RC8-H-406RP	05309	CLAMP CUSH GE24449/13407-JM-RP	
	10097	CRES 321 ANN SHT PLT STRIP	
JM44SP4-H310RP	05309	CLAMP CUSH GE24449/13407-JM-RP	
	10097	CRES 321 ANN SHT PLT STRIP	
K50673	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER FASTENERS ONLY	
K7001	10267	CRES A286 FASTENER MATL ONLY	
	00597	LUBE DRY	
KA-89-63	30080	CRES 303 FREE MACHINING	
KBDEX-200CR	10399	CRES 17-4PH H1025 BAR FRG RING	
	10416	CRES 17-4PH H1150 BAR ROD FORG	
	30008	CRES 440C RC 58 BAR FRG	
	05053	LUBE LINER KAHR-LON X1200S	
	30082	PLATING CADMIUM & CHROMATE	
KC103-XX	00016	TEFLON TFE	SEAL RING
KC106CXX-XX	10370	CRES 316 COND A & B BAR	REDUCER-ADAPTER
KC107CXX	10370	CRES 316 COND A & B BAR	TEE-ASSEMBLY
	10148	SPRING 302 COND B WIRE	
KC108CXX	10294	CRES 302 ANN THRU 1/2 HD PT SH	ELBOW ASSY,90DEG
	10370	CRES 316 COND A & B BAR	
KC109CXX	10370	CRES 316 COND A & B BAR	TEE ASSEMBLY
	10148	SPRING 302 COND B WIRE	
KC110CXX	10294	CRES 302 ANN THRU 1/2 HD PT SH	TEE-ASSEMBLY
	10370	CRES 316 COND A & B BAR	
KC111CXX	10294	CRES 302 ANN THRU 1/2 HD PT SH	TEE ASSEMBLY
	10370	CRES 316 COND A & B BAR	
KC112CXX	10370	CRES 316 COND A & B BAR	ADAPTER, TUBE
KC113CXX	10370	CRES 316 COND A & B BAR	ELBOW, TUBE

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
KC115CXX-XX	10370	CRES 316 COND A & B BAR	BUSHING
KC116CXX-XX	10370	CRES 316 COND A & B BAR	NIPPLE
KC119CXX	10370	CRES 316 COND A & B BAR	TEE, FLARED TUBE
KC120CXX	10370	CRES 316 COND A & B BAR	TEE, FLARED TUBE
KC124CXX	10370	CRES 316 COND A & B BAR	UNION-FLRD TUBE
KC125CXX-XX	10370	CRES 316 COND A & B BAR	REDUCER, TUBE
KC126CXX	10370	CRES 316 COND A & B BAR	UNION-FLRD TUBE
KC127CXX	10370	CRES 316 COND A & B BAR	TEE, FLARED TUBE
KC129CXX	10294	CRES 302 ANN THRU 1/2 HD PT SH	ELBOW ASSEMBLY
	10370	CRES 316 COND A & B BAR	
KC130CXX	10370	CRES 316 COND A & B BAR	PLUG,FLARED TUBE
KC131CXX	10370	CRES 316 COND A & B BAR	ELBOW ASSEMBLY
	10148	SPRING 302 COND B WIRE	
KC133CXX-XX	10370	CRES 316 COND A & B BAR	REDUCER-ADAPTER
KC134CXX	10370	CRES 316 COND A & B BAR	ADAPTER,FL TUBE
KC135CXX-XX	10370	CRES 316 COND A & B BAR	EXPANDER-ADAPTER
KC140CXX	10294	CRES 302 ANN THRU 1/2 HD PT SH	WASHER
KC142CXX	10370	CRES 316 COND A & B BAR	NUT,COUPLING
KC143CXX	10370	CRES 316 COND A & B BAR	SLEEVE
KMDB44-1	10416	CRES 17-4PH H1150 BAR ROD FORG	
	10106	CRES 440C RC 55 BAR VAR	
	00597	LUBE DRY	
	05053	LUBE LINER KAHR-LON X1200S	
	10275	PLATING CHROMIUM (CLASS 2)	
KN	30080	CRES 303 FREE MACHINING	
KNB-5LR	06195	SOUND INSUL KNB-5LR PVC/GL/PB	
KNJ	10391	CRES 302/304/316 SHT PLT WIRE	
	30080	CRES 303 FREE MACHINING	
KNKDLXXXT-NE	10267	CRES A286 FASTENER MATL ONLY	INSERT,FLOATING
	20247	LUBE DRY ON METALLIC FASTENRS	
KNKLXXXXT-NE	10267	CRES A286 FASTENER MATL ONLY	INSERT,FLOATING
	20247	LUBE DRY ON METALLIC FASTENRS	

MSFC-HDBK-527 REV F 9999942 0007041 3

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
KNL	10315	CRES 302/304/316 FASTENRS ONLY	
	30080	CRES 303 FREE MACHINING	
	05723	LUBE DRY	
KNXLXXXXT-XSP	10267	CRES A286 FASTENER MATL ONLY	INSERT
	05723	LUBE DRY	
	10281	PLATING SILVER FASTENERS ONLY	
KN7DJ-X	10294	CRES 302 ANN THRU 1/2 HD PT SH	
	30080	CRES 303 FREE MACHINING	
	00016	TEFLON TFE	
KOLN 18T	05617	GLASS	GLASS STRIPS
KOLN XXT	05617	GLASS	GLASS STRIPS
KXLX	10350	CRES 301/302 ANN SHT STDS ONLY	
L4650-1	10315	CRES 302	RING RETAINING
L58819-X	10267	CRES A286 FASTENER MATL SH	NUT,DRILLED JAM
	10281	PLATING SILVER	
LAB48836N	10223	NI COATED CU/NICKEL WIRE	
LC-032C	99011	SEE FILE FOR MATERIALS	
LC-033C	99011	SEE FILE FOR MATERIALS	
LC-034C	99011	SEE FILE FOR MATERIALS	
LC-035C	99011	SEE FILE FOR MATERIALS	
LC-036C	99011	SEE FILE FOR MATERIALS	
LC-037C	99011	SEE FILE FOR MATERIALS	
LC-038C	99011	SEE FILE FOR MATERIALS	
LD112-0029	10267	CRES A286 FASTENER MATL ONLY	
LD112-0030	10267	CRES A286 FASTENER MATL ONLY	
LD114-0005-10XX	30080	CRES 303 FREE MACHINING	
LD114-0006-10XX	30080	CRES 303 FREE MACHINING	
LD114-0007-10XX	30080	CRES 303 FREE MACHINING	
LD114-0008-10XX	30080	CRES 303 FREE MACHINING	
LD122-0003-01XX	10148	SPRING 302 COND B WIRE	
LD122-0003-02XX	10148	SPRING 302 COND B WIRE	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
LD122-0003-03XX	10148	SPRING 302 COND B WIRE	
LD122-0003-04XX	10148	SPRING 302 COND B WIRE	
LD122-0003-05XX	30080	CRES 303 FREE MACHINING	
LD122-0003-06XX	30080	CRES 303 FREE MACHINING	
LD122-0003-07XX	30080	CRES 303 FREE MACHINING	
LD122-0003-08XX	30080	CRES 303 FREE MACHINING	
LD122-0003-09XX	30080	CRES 303 FREE MACHINING	
LD122-0003-10XX	30080	CRES 303 FREE MACHINING	
LD137-0037	10257	AL-BRONZ 110KSI BEARING SHP BR	
LD137-0038	10257	AL-BRONZ 110KSI BEARING SHP BR	
LD137-0040	10430	CRES 17-4PH H1075 BR (RES 266)	
LD152-0001-10XX	10500	AL 5052-0 OR 6061-T4 TUBE	SPACER
	10277	COATING ANODIC TYPE 2	
LD152-0019-0250	30112	2024-T3 AL	SPACER
	30112	2024-T4 AL	
	10277	ANODIZE	
	05022	ZINK CHROMATE PRIMER	
LD152-0019-0450	30112	2024-T3 AL	SPACER
		2024-T4 AL	
	10277	ANODIZE	
	05022	ZINK CHROMATE PRIMER	
LD153-0002-2XXX	10097	CRES 321 ANN SHT PLT STRIP	
	05486	DYE GREEN	
LD153-0005	10134	NI INCO 600 ANN SHT PLT STP	WASHER
LD153-0010	10097	CRES 321 ANN SHT PLT STRIP	WASHER
	05486	DYE GREEN	
LD153-0011	10028	AL 7075-T6 SHEET	
	10277	COATING ANODIC TYPE 2	
	20065	DYE RED	
LD153-0013-XXXX	10267	A286 CRES	WASHER
	10267	A286 CRES	
	05486	GREEN DYE	
LD153-0017	10333	CU SHT PLT BAR ANN	
	10308	PLATING NICKEL ELECTRODEPOSIT	
LD153-0029	30014	CRES PH15-7MO RH 1050/1075	

MSFC-HDBK-527 REV F 9999942 0007043 7

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
LD191-0002	10350	CRES 301/302 ANN SHT STDS ONLY	
LD273-0334	10390	CRES 321/347 ANN BR PLT TB	
LD495010N	10308	PLATING NICKEL ELECTRODEPOSIT	
	10648	STEEL 1008-1020	
LDU52-0019-0450	30112		
LHC FMI-2860	10276	CRES A286	NUT,CLINCH
LHSSVV-XX	30080	CRES 303 FREE MACHINING	
	10351	CRES 304 ANN BAR SHP FRG WIRE	
	10106	CRES 440C RC 55 BAR VAR	
	05053	LUBE LINER KAHR-LON X1200S	
LN 1434	10109	STEEL 4130	BOLT
LN 1798	10408	AL 2024/T3	INSERT
LN 1799	10408	AL 2024-T3	INSERT
LN 2166	10279	AL 1100	WASHER
LN 29540	10476	CRES 17-4PH H1025	INSERT
	05520	LUBE DRY TIO LUBE 460	
LN 29557	10252	AL 1050	SHIM LAMINATED
LN 29557 B	50357	ALCOA 5052	SHIM
LN 29557 TYP 1	50085	CRES 304	LAMINATED SHIM
LN 29557 TYP 3	10252	AL 1100	LAMINATED SHIM
LN 29559	00666	ALODINE 1200	SHIM
	10267	CRES A286	
LN 29638	10097	CRES 321	NUT,PRESS
LN 29668	10124	CRES A286	NUT
LN 29669	10109	STEEL 4130	NUT
LN 29671	50108	PLATING TIN LEAD	NUT
	10108	STEEL 4130	
LN 29671 TYPE 091	10069	TI 6AL 4V	NUT
LN 29672	10097	CRES 321	NUT
	50108	PLATING TIN-LEAD	
LN 29672 TYPE 081	10097	CRES 321	NUT
LN 29673	50108	PLATING TIN-LEAD	NUT
	10108	STEEL 4130	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
LN 29673 TYPE 081	10097	CRES 321	NUT
LN 29675	50108 10108	PLATING TIN-LEAD STEEL 4130	NUT
LN 29675 TYPE 085	10097	CRES 321	NUT
LN 29675 TYPE 095	10069	TI 6AL 4V	NUT
LN 29681	10109	STEEL 4130	NUT
LN 29691	10069 10039	CRES A286 SILVER PLATED	NUT
LN 29692	10124	CRES A286	NUT
LN 29693	10124	CRES A286	NUT
LN 29695	10001	CRES 15-7PH	NUT
LN 29784	10069	TI 6AL 4V	BOLT
LN 29787	10069	TI 6AL 4V	SCREW
LN 29788	10124 10039	CRES A286 PLATING SILVER	NUT
LN 29789	10039 10687	PLATING SILVER STEEL SHEET AND STRIP LOW CARB	RETAINING SPRING
LN 29792	10069	TI 6AL 4V	BOLT , HEX
LN 29796	10069	TI 6AL 4V	PIN , HEAD
LN 29797	10069	TI 6AL 4V	BOLT , HEAD
LN 29798	50055	AL 2024-T6	COLLAR
LN 29928	50055	AL 2024/T62	COLLAR
LN 29933 L	50092 10277	AL 2024 CTNG ANODIC TYPE 2	PLATE
LN 29933 S	10097	CRES 321	PLATE
LN 29940	10097	CRES 321	SCREW
LN 29943	05886 10069	DRY LUBE MOLYCOTE X-106 TI 6AL 4V	BOLT
LN 29943-1	10069	TI 6AL 4V	SCREW
LN 29949	10124	CRES A286	SCREW , CHEESE
LN 29950	10069	TI 6AL 4V	SCREW , CHEESE

MSFC-HDBK-527 REV F ■ 9999942 0007045 0 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
LN 29952 L	10408	AL 2024	WASHER
LN 29952 M	10097	CRES 321	WASHER
LN 29955	10267	CRES A286	BOLT , BI-HEX
LN 29956	10069	TI 6AL 4V	BOLT
LN 29957	10069	TI 6AL 4V	BOLT , PAN HEAD
LN 29958	05586 10069	DRY LUBE MOLYCOTE X-106 TI 6AL 4V	SCREW , PAN-HEAD
LN 29960	10359	STEEL AISI/SAE 1010 TO 1040	BOLT
LN 29966	05776	BORON NITRIDE	SCREW
LN 29989	05826 30082 50246	LUBE DRY ELECTROFILM 5306 PLATING CADMIUM & CHROMATE STEEL 1050	NUT
LN 29990	10124	CRES A286	NUT
LN 29991	10124	CRES A286	NUT
LN 29992	10124	CRES A286	NUT
LN 29996	10124	CRES A286	NUT
LN 6166	10279	AL 1100	WASHER
LN 65045	10413	CRES 304	SHIM,WASHER
LN 65049 L	50092	AL 2024	WASHER
LN 65049 M	10097	CRES 321	WASHER
LN 65057	10124 05886	CRES A286 (1.4944.4) DRY LUBE MOLYCOTE X-106	NUT, BI-HEX
LN 65072	10069	TI 6AL 4V	BOLT
LN 65407	10124	CRES A286	NUT
LN 65410		TI 6AL 4V	NUT
LN 9016 L	10097	CRES 321	WASHER
LN 9016 M	10124	CRES A286	WASHER
LN 9023	10097	CRES 321	WASHER , LOCKING
LN 9023 B10	10097	CRES 321	LOCKING WASHER
LN 9025	10069	TI 6AL 4V	WASHER

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
LN 9025 N	50092	AL 2024	WASHER
LN 9025L	10097	CRES 321	WASHER
LN 9037	10109	STEEL 4130	SCREW
LN 9039	10294	CRES 302	INSERT
LN 9073	10421	AL 7075-T7351	CLAMP
LN 9136	10097	CRES 321	SCREW , PHILLIPS
LN 9136 M	10069	TI 6AL 4V	SCREW
LN 9139	10098	CRES 321	BOLT
LN 9161	10124	CRES A286	NUT
LN 9166	10366	AL 1100	WASHER
LN 9178	10223	NI ALLOY	RIVET
LN 9179	10223	NI ALLOY	RIVET CSK' 100
LN 9198	10217	AL 1100	RIVET
LN 9198 BF	10335	AL 2117-T4	RIVET
LN 9198 CF	30111	AL 2024-T4	RIVET
LN 9198 DF	10443	AL 5056	RIVET
LN 9199	30111	AL 2024-T4	RIVET
LN 9199 B	10335	AL 2117-T4	RIVET
LN 9199 BF	10335	AL 2117-T4	RIVET
LN 9199 CF	30111	AL 2024-T4	RIVET
LN 9199 EF	10335	AL 2117-T4	RIVET
LN 9199 HF	10279	AL 1100	RIVET
LN 9240	60098	RUBBER NBR INSULATION	GROMMET
LN 9262	50114 20017	CU TERMINAL LUG (TINNED) POLYOLEFIN TUBING HST	TERMINAL LUG
LN 9264	10354	COPPER WIRE	GROUNDING LEAD
LN 9317	10335	AL 2117-T4	RIVET
LN 9338	10124	CRES A286	NUT , HEX

MSFC-HDBK-527 REV F 9999942 0007047 4

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
LN 9339	10124	CRES A286	NUT , SELF-LOCKING
LN 9342	50361	STEEL 1035 (.35C-.75MG-.20SI)	NUT
LN 9345	50361	STEEL 1035 (.35C-.75MG-.20SI)	NUT
LN 9367	10106	CRES 440 C	BALL BEARING
LN 9386	10069	TI 6AL 4V	BOLT , HEX
LN 9389	10520	CRES 302	WIRE
LN 94	10262	CRES 302	PIN,COTTER
LN 9406	60069	TEFLON (PTFE)	PLUG
LN 9424	10097	CRES 321	WIRE LOCKING
LN 9434 M	10069	TI 6AL 4V	SCREW
LN 9438	10109	STEEL 4130	SCREW
LN 9439	10069	TI 6AL 4V	SCREW , PAN-HEAD
LN 9441	05520 10069 10649	LUBE DRY TID LUBE TI 6AL 4V TIODIZE ANODIC COATING	SCREW,FLAT
LN 9442	10069	TI 6AL 4V	SCREW
LN 9498	10217	AL 1100	RIVET
LN 9499	10294	CRES 302	INSERT
LN29671 TYPE 081	10097	CRES 321	NUT
LN29672 TYPE 091	10069	TI 6AL 4V	NUT
LN29673 TYPE 091	10069	TI 6AL 4V	NUT
LP-EU6-7	10124 10039	CRES A286 PLATING SILVER	BOLT
LS 40563	50259 20121	AL 2024-T42 CLAD SHEET PLATE RUBBER SILICONE	CLAMP
LS 41164-205	10325	AL 6061 ANN SHT & PLT	CONNECTOR
LS 41514-6	60075	LAMIN PHENOLIC/COTTON TYPE FBM	WASHER
LS 41526-003	06541	CERAMIC BERYLLIUM OXIDE	WASHER,INSULATION
LS 41561-004	65536	RUBBER ADIPRENE 9006	POLYURETHANE CAP
LS 41563-001	65556	RUBBER ADIPRENE 9006	POLYURETHANE CAP

MSFC-HDBK-527 REV F 9999942 0007048 6

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
LS 41629CB	10267	CRES A286 FASTENER MATL SH	NUT
	10281	PLATING SILVER	
LS 42623-04	10267	CRES A286 FASTENER MATL SH	1CB NUT
	10281	PLATING SILVER	
LS 42632-06-1	10267	CRES A286 FASTENER MATL SH	NUT
	10281	PLATING SILVER	
LS 8047-134	05005	RUBBER VITON FLUID RESISTANT	GASKET
LS 8761-X	10267	CRES A286 FASTENER MATL SH	BOLT
LS-8971-4-9-0	10267	CRES A286 FASTENER MATL SH	BOLT
LS40515C04-2	30080	CRES 303 BAR FRG FREE MACHINE	SPACER
LS41197	10321	BRASS	FUSE
	10322	BRONZE	
	20086	CERAMIC INSULATOR MATERIAL	
	10354	COPPER	
	10328	PLATING GOLD	
	60299	TUBING POLYVINYLIDENE FLUORIDE	
LS41306	10321	BRASS	SENSOR,CURRENT
	10354	COPPER WIRE	
	60179	FOAM URETHANE	
	10328	PLATING GOLD	
	10039	PLATING SILVER	
	60422	POLY (AMIDE-IMIDE)	
	61626	RUBBER FLUOROCARBON	
	50113	STEEL 1020/1025	
LS41513	50114	CU TERMINAL	LUG,CRIMP STYLE
	10328	PLATING GOLD	
	00367	TUBING KYNAR HST	
LS41516EX-X	10443	AL 5056-O ROD & WIRE	RIVET,BLIND PROTR.HEAD
	10135	INCO 600	
	05638	LUBE DRY TRANSLUBE 20204	
	10222	MONEL	
LS41529	60177	ADHES EA 901	SWITCH
	10050	AL 356-T51	
	10022	AL 6061-T6	
	10638	BE-CU 175	
	10354	COPPER	
	10268	CRES 300 SERIES	
	30008	CRES 440C	
	61066	CTNG URETHANE	
	05128	GREASE BRAYCO 3L-38RP	
	20023	INSUL WIRE POLYOLEFIN/KYNAR	
	01883	LAMIN EPOXY/GLASS	
	10328	PLATING GOLD	
	10046	PLATING NI ELECTROLESS	

MSFC-HDBK-527 REV F 9999942 0007049 8

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
LS41531CXPX	10267	CRES A286 FASTENER MATL SH	WASHER
LS41531DXXX	50259	AL 2024-T42 CLAD SHEET PLATE	WASHER
LS41532	10267	CRES A286 FASTENER MATL SH	NUT
LS4153CXXX	10267	CRES A286 FASTENER MATL SH	WASHES
LS41550	50259 61142	AL 2024-T42 CLAD TAPE TA-88	CLAMP,LOOP CUSHIONED
LS41551	10350 05205	CRES301/302 TEFZEL (ETFE)	STRAP,ELECTRICAL
LS41553	10267 05520 10281	CRES A286 FASTENER MATL. SH. DRY LUBE TIO LUBE 460 MS21063 PLATING. SILVER	NUT, HEXAGON CAP
LS41554-XS	10267 05520 10281	CRES A-286 LUBE DRY TIOLUBE 460 PLATING SILVER	NUT, HEXAGON CAP,
LS42599ADXT	10335 00666	AL 2117-T4 ANN ROD&WIRE COATING CONV. CHROMATE	RIVET,SOLID UNIV. HEAD
LS42599BX	50275 00666	AL 5056 BAR ROD WIRE COATING CONVERSION CHROMATE	RIVET,SOLID UNIV. HEAD
LS42600ADX	10335 00666	AL 2117-T4 ANN ROD&WIRE COATING CONVERSION CHROMATE	RIVET
LS42600BX	50275 00666	AL 5056 BAR ROD&WIRE COATING CONVERSION CHROMATE	RIVET
LS42622	10267 05520 10281	CRES A286 FASTENER MATL SH LUBE DRY T10 LUBE 460 MS21063 PLATING SILVER	NUT
LS42624	10267 10281	CRES A-286 PLATING SILVER	NUT, NON-LOCKING PLATE
LS42628	10267 10281	CRES A286 FASTENER MATL SH PLATING SILVER	NUT
LS42630-X-X	10267 10281	CRES A286 FASTENER MATL SH PLATING SILVER,FASTENERS	NUT
LS42631	10267 10281	CRES A286 FASTENER MATL SH PLATING SILVER	NUT
LS42634-X-X	10267 10281	CRES A286 FASTENER MATL SH PLATING SILVER	NUT
LS42636	10267 10281	CRES A286 FASTENER MATL SH PLATING SILVER	NUT

MSFC-HDBK-527 REV F 9999942 0007050 4

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
LS42637-XCB	10267 05520 10281	CRES A286 FASTENER MATL SH LUBE DRY T10 LUBE 460 MS21063 PLATING SILVER	NUT
LS42638	10267 10281	CRES A286 PLATING SILVER	NUT, HEXAGON NUT LOCK
LS42639-CB	10267 10281	CRES A286 FASTENER MATL SH PLATING SILVER	NUT
LS42642C0XLX	10267 10281	CRES A286 FASTENER MATL SH PLATING SILVER	NUT
LS42643-CB	10267 10281	CRES A286 FASTENER MATL SH PLATING SILVER	NUT
LS42644	10267 10281	CRES A286 FASTENER MATL SH PLATING SILVER	NUT
LS42652CXLX	10267 05123	CRES A286 VESPEL SP-1	BOLT, SELF LOCKING,
LS42652VXLV	10365 05123	TI 6AL 4V BAR FORGE VESPAL SP-1/POLYIMIDE-CV	BOLT SELF-LOCKING
LS42653CXLX	10267 10365	CRES A286 FASTENER MATL SH TI 6AL 4V BAR FORGE	BOLT NON-LOCKING
LS42654CXIX	10267 05123	CRES A286 VESPEL SP-1	BOLT, SELF-LOCKING
LS42655CXLX	10267	CRES A286 FASTENER MATL SH	BOLT
LS42656CXLX	10267 05123	CRES A286 FASTNER MATL SH VESPEL SP-1/POLYIMIDE	BOLT,SELFLOCKING
LS42656VXLX	10365 05123	TI 6AL 4V BAR FORGE VESPAL SP-1/POLYIMIDE	BOLT SELF-LOCKING
LS42660CXLX	10267 05123	CRES A286 FASTENER MATL SH VESPAL SP-1/POLYIMIDE-CU	12 POINT HEAD
LS42664	10267 10281	CRES A286 FASTENER MATL SH PLATING SILVER	NUT
LS42671C02-5	10267	CRES A286 FASTENER MATL SH	BOLT
LS42672CXLX	10267 05123	CRES A286 VESPEL SP-1	BOLT, SELFLOCKING
LS42672VXLX	10365 05123	TI 6AL 4V BAR FORGE VESPAL SP-1/POLYIMIDE	BOLT SELF-LOCKING
LS42678CXLX	10267 10365	CRES A286 FASTENER MATL SH TI 6AL 4V BAR FORGE	BOLT

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
LS42679CXLX	10267	CRES A286	BOLT, SELF-LOCKING
	05123	VESPEL SP-1	
LS42679VXLX	10365	TI 6AL 4V BAR FORGE	BOLT SELF-LOCKING
	05123	VESPAL SP-1/POLYIMIDE	
LS42684-4	10409	CRES 17-7 CH900 SHT STP	RETAINER ASSY
	10267	CRES A286 FASTENER MATL SH	
LS42692-XX	65557	LUBE HI COAT 292	HI-LOK PIN
	10365	TI 6AL 4V BAR FORGE	
LS42694	65557	LUBE HI COAT 292	PIN
	10365	TI 6AL 4V BAR FORGE	
LS42695	65557	LUBE HI COAT 292	PIN
	10365	TI 6AL 4V BAR FORGE	
LS42696	10292	AL 2024-T6 BAR ROD & WIRE	COLLAR
	65557	LUBE HI COAT 292	
LS42697	30080	CRES 303 BAR FRG FREE MACHINE	COLLAR
	65557	LUBE HI COAT 292	
LS42698-R	30080	CRES 303 BAR FRG FREE MACHINE	COLLAR
	65557	LUBE HI COAT 292	
LS600 TO LS608	05929	POTTG CPD PHENOLIC FM 1132	WASHER
LS8565-X	10294	CRES 302 ANN THRU 1/2 H PLATE	SHIM
LS8695	10112	AL 5052-H32 SHEET & PLATE	WASHER
LS8752	10267	CRES A286 FASTENER MATL SH	SCREW
	05084	KEL-F UNPLASTICIZED	
LS8763-XXX	10267	CRES A286 FASTENER MATL SH	BOLT
	05084	KEL-F UNPLASTICIZED	
LS8775	50114	COPPER	LUG,TERMINAL
	60137	PLASTIC POLYVINYL CHLORIDE	
	10328	PLATING GOLD	
LS8778-XXXX	10267	CRES A286 FASTENER MAT SH	SET SCREW
	05084	KEL-F UNPLASTICIZED	
LS8830	10267	CRES A286 FASTENER MATL SH	NUT
	10281	PLATING SILVER	
LS8835	10267	CRES A286 FASTENER MATL SH	NUT
	10281	PLATING SILVER	
LS8837	10267	CRES A286 FASTENER MATL SH	NUT
	10281	PLATING SILVER	

MSFC-HDBK-527 REV F 9999942 0007052 8

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
LS8846	10267 10281 05343	CRES A286 FASTERER MATL SH PLATING SILVER RUBBER 8604-70 SILICONE	NUT, SELF-LOCKING
LS8859	10267 10281	CRES A286 FASTENER MATL SH PLATING SILVER	NUT SELF-LOCKING
LS8884-1	30080 10281	CRES 303 BAR FRG FREE MACHINE PLATING SILVER	NUT
LS8889-08A	10267 10281	CRES A286 FASTENER MATL SH PLATING SILVER	NUT
LS8892PXX	10267 00881	CRES A286 FASTENER MATL SH LUBE DRY EVERLUBE 812	RIVET
LS8896	50259 20121	AL 2024-T42 CLAD SHEET PLATE RUBBER SILICONE	CLAMP
LS8911-2	30080	CRES 303 BAR FRG FREE MACHINE	SPACER
LS8961	10321	BRASS AL FORMS	TERMINAL,STUD SWAGE
LS8962	10321	BRASS AL FORMS	TERMINAL,STUD,SWAGE
LS8971-4-9-0	10267 10281	CRES A286 FASTENER MATL SH PLATING SILVER	RECEPTACLE
LS8999	10267	CRES A286 FASTENER MATL SH	WASHER
LW 2600	10315 10275	CRES 302 PLATING CHROMIUM	WASHER
M 45932 B	10217 05520	BE-CU DRY LUBE	INSERT
M 45932 C	10267 10039	CRES A286 SILVER PLATING	INSERT
M 45932 L	10471 05520	CRES 17-4 PH DRY LUBE	INSERT
M 7078	05179	INSUL WIRE AG PLATE TFE/POLYIM	CABLE
M 81381	05179	INSUL WIRE AG PLATE TFE/POLYIM	WIRE
M13740	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENER ONLY	
M137R	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENER ONLY	
M45932 A	30082 10300	CADMIUM PLATING STEEL 4130	INSERT

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
M45932/1-9CL	10125	CRES A286	INSERT
	10039	SILVER PLATE	
M5159T1-2M	10095	CRES 316 ANN SHT PLT STRIP	
	20238	RUBBER 5-565 BUNA N	
	10147	SPRING 17-7PH CH900 WIRE STP	
M7078/11	05179	INSUL WIRE AG PLATE TFE/POLYIM	CABLE,ELECTRIC
M81381/9	62251	INSUL WIRE NI PLATE TFE/POLYIM	INSUL ELECTRIC CABLE
M81934/X-XXA	10508	AL 2024-T8511 BAR	
	10277	COATING ANODIC TYPE 2	
	00016	TEFLON TFE	
M81934/X-XXC	10416	CRES 17-4PH H1150 BAR ROD FORG	
	00016	TEFLON TFE	
M81935/1	10399	CRES 17-4PH H1025 BAR FRG RIN	
	30008	CRES 440C RC 58 BAR FRG	
	05053	LUBE LINER KAHR-LON X1200S	
	30082	PLATING CADMIUM & CHROMATE	
	10486	STEEL 4340,4140,4130,8740	
M83248	61626	RUBBER FLUOROCARBON	SEAL
M83248/1	05005	RUBBER VITON FLUID RESISTANT	
M83248/2	05005	RUBER VITON FLUID RESISTANT	
M83723	99011	SEE FILE FOR MATERIALS	
M85/1-091	10371	AL 6061/6063-T6 (WAVEGUIDE)	
MA13700	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER FASTENERS ONLY	
MB9325KXXXJ	10095	CRES 316 ANN SHT PLT STRIP	
MC 124	10370	CRES 316	NUT COUPLING
MC 125	10267	CRES A286	SLEEVE
	60150	LUBE KRYTOX 240AC	
MC 160C	10370	CRES 316	UNION
MC 164	10370	CRES 316	UNION , FLARED
MC 165	10370	CRES 316	UNION , FLARED
MC 169	10268	CRES 300 SERIES	REDUCER
MC 174	10370	CRES 316	NUT , FLARED TUBE
MC 177	10370	CRES 316	CAP ASSEMBLY

MSFC-HDBK-527 REV F 9999942 0007054 1

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MC 239	10370	CRES 316	UNION , RACCORDO
MC 240	10268	CRES 300 SERIES	BOSS
MC 252 C	10351	CRES 304	GASKET
	60069	TEFLON COATING	
MC 659	10482	AL 6061-T6	U-BOLT STRAP TYPE
	10276	ANODIC CTNG	
MC238DXX	10047	AL 7075-T73XX RLD/DWN BAR ROD	PLUG & BLEEDER
	10277	COATING ANODIC TYPE 2	
MC621-0024-XXXX	10399	17-4PH CRES	QUICK COUPLING
	10147	17-7 PH CRES	
	10409	17-7 PH CRES	
	10095	316 CRES	
	10098	321 CRES	
	10025	6061-T6 AL	
	10276	ANODIZE T1	
	05668	BUNAN	
	00016	TFE TEFLON	
MD 40	10469	CU WIRE AG PLATE SOFT OR ANN	WIRE ELEC.
	60434	POLYIMIDE-CU	
MD 45	10330	CU WIRE TIN PLATED	ELEC. BUS WIRE
MD 802	10354	CU WIRE ALLOY 102	BRAID,WIRE
MD 920	10469	CU WIRE AG PLATE SOFT OR ANN	CONDUCTOR 600 VOLTS
	60422	POLY (AMIDE-IMIDE)	
	60434	POLYIMIDE-CU	
MD111-0002	10267	CRES A286 FASTENER MATL ONLY	
MD111-0003-2XX1	10088	CRES 301 ANN THRU 1/2 HD PT SH	
	30080	CRES 303 FREE MACHINING	
	10267	CRES A286 FASTENER MATL ONLY	
MD111-003-3XX1	10088	CRES 301 ANN THRU 1/2 HD PT SH	
	30080	CRES 303 FREE MACHINING	
	10267	CRES A286 FASTENER MATL ONLY	
MD111-1001	10424	NI STA INCO 718 FASTENER ONLY	
	10275	PLATING CHROMIUM (CLASS 2)	
MD111-1002	10424	NI STA INCO 718 FASTENER ONLY	
	10275	PLATING CHROMIUM (CLASS 2)	
MD111-1006	10424	NI STA INCO 718 FASTENER ONLY	
MD111-3001	10123	MULTIPHASE MP35N SOL TREATED	
MD111-3002	10132	NI U-500 ST BAR & FORGING	

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD111-3003	10424	NI STA INCO 718 FASTENER ONLY	
MD111-4001	10267	CRES A286 FASTENER MATL ONLY	
MD111-4019	10123	MULTIPHASE MP35N SOL TREATED	
MD111-4020	10123	MULTIPHASE MP35N SOL TREATED	
MD111-4021	10123	MULTIPHASE MP35N SOL TREATED	
MD111-4022	30007	NI U-500 BAR FASTENERS ONLY	
MD111-4023	30007	NI U-500 BAR FASTENERS ONLY	
MD111-4024	10123	MULTIPHASE MP35N SOL TREATED	
MD111-4025	10424	NI STA INCO 718 FASTENERS ONLY	
MD111-4026	10424	NI STA INCO 718 FASTENERS ONLY	
MD111-4027	10424	NI STA INCO 718 FASTENERS ONLY	
MD112-1001	10268	CRES 300 SERIES FASTENER MATL	
MD112-1002	10267	CRES A286 FASTENER MATL ONLY	
MD112-1003	10267	CRES A286 FASTENER MATL ONLY	
MD112-3002	10267	CRES A286 FASTENER MATL ONLY	
MD112-3003	10267	CRES A286 FASTENER MATL ONLY	
MD112-3004	10384	NI INCO 718 ST/STA BAR	
MD112-5001	10267	CRES A286 FASTENER MATL ONLY	
MD112-6002	10267	CRES A286 FASTENER MATL ONLY	
MD113-0001	30080	CRES 303 FREE MACHINING	
MD114-0002	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENERS ONLY	
MD114-1001	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENERS ONLY	
MD114-1002	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENERS ONLY	
MD114-3001	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENERS ONLY	
MD114-3004-01XX	10267 05072	CRES A286 FASTENER MATL ONLY LUBE DRY NA SILICATE BASE INOR	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD114-3004-10XX	10424	NI STA INCO 718 FASTENERS ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-3004-11XX	05072.	LUBE DRY NA SILICATE BASE INOR	
	10424	NI STA INCO 718 FASTENERS ONLY	
MD114-3005-00XX	10424	NI STA INCO 718 FASTENERS ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-3005-01XX	05072	LUBE DRY NA SILICATE BASE INOR	
	10424	NI STA INCO 718 FASTENERS ONLY	
MD114-3007-00XX	10384	NI INCO 718 ST/STA BAR	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-3007-01XX	05072	LUBE DRY NA SILICATE BASE INOR	
	10384	NI INCO 718 ST/STA BAR	
MD114-304-00XX	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-4001	10097	CRES 321 ANN SHT PLT STRIP	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-4002	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	10277	COATING ANODIC TYPE 2	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-5001	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-5002	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-5003	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-5004	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-5005	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-5006	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
	02976	RUBBER SILICONE	
MD114-5007	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-5008	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	

MSFC-HDBK-527 REV F ■ 9999942 0007057 7 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD114-5009	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-5010	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-5011	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
	05005	RUBBER VITON FLUID RESISTANT	
MD114-5012	10267	CRES A286 FASTENER MATL ONLY	
	10132	NI U-500 ST BAR & FORGING	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-5013	10267	CRES A286 FASTENER MATL ONLY	
	10424	NI STA INCO 718 FASTENERS ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-5014	10267	CRES A286 FASTENER MATL ONLY	
	10424	NI STA INCO 718 FASTENERS ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-5015	10456	CRES A286 130 KSI BAR FRG TUB	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-5016	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD114-6001-0002	10351	CRES 304 ANN BAR SHP FRG WIRE	
MD114-6001-0003	10351	CRES 304 ANN BAR SHP FRG WIRE	
	05402	CTNG POLYU BLACK COLOR 37038	
	05135	PRIMER EPOXY/POLYAMIDE	
MD115-2002	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MD121-0001	10036	AL 2219-T8511/6X EXT PRODUCTS	
	00666	CTNG CONVERSION CHROMATE INORG	
MD121-0002	10036	AL 2219-T8511/6X EXT PRODUCTS	
	00666	CTNG CONVERSION CHROMATE INORG	
MD121-0003	10036	AL 2219-T8511/6X EXT PRODUCTS	
	00666	CTNG CONVERSION CHROMATE INORG	
MD121-0004	10267	CRES A286 FASTENER MATL ONLY	
	00098	LUBE DRY 905 (INORGANIC)	
MD121-0005	10267	CRES A286 FASTENER MATL ONLY	
	00098	LUBE DRY 905 (INORGANIC)	
MD122-0004	10267	CRES A286 FASTENER MATL ONLY	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD122-0007	10267	CRES A286 FASTENER MATL ONLY	
	05046	LUBE DRY CORR. INH.	
MD122-0010	05172	TEFLON PFA 340 FLUOROCARBON	
MD122-0011	05172	TEFLON PFA 340 FLUOROCARBON	
MD122-0012	10156	CRES 17-4PH 150KSI CSTG INV	
MD122-0013	10123	MULTIPHASE MP35N SOL TREATED	
MD122-1001	10267	CRES A286 FASTENER MATL ONLY	
MD123-0002-0001	05172	TEFLON PFA 340 FLUOROCARBON	
MD124-0001	10382	CRES 302 ANN BAR SHP FRG WIRE	
	05046	LUBE DRY CORR. INH.	
MD126-0004	10205	AL 2024-T8XX SHT&PLT(NOT T86X)	
	10036	AL 2219-T8511/6X EXT PRODUCTS	
	10277	COATING ANODIC TYPE 2	
	10267	CRES A286 FASTENER MATL ONLY	
	00666	CTNG CONVERSION CHROMATE INORG	
	10281	PLATING SILVER,FASTENERS ONLY	
MD127-0041	10101	CRES 321 ANN TUBING SEAMLESS	
	02151	TUBING TFE HST	
MD127-0042	10101	CRES 321 ANN TUBING SEAMLESS	
	02151	TUBING TFE HST	
MD127-0043	10101	CRES 321 ANN TUBING SEAMLESS	
	02151	TUBING TFE HST	
MD127-0044	10101	CRES 321 ANN TUBING SEAMLESS	
	02151	TUBING TFE HST	
MD127-0045	10101	CRES 321 ANN TUBING SEAMLESS	
	02151	TUBING TFE HST	
MD127-0046	10101	CRES 321 ANN TUBING SEAMLESS	
	02151	TUBING TFE HST	
MD127-0047	10101	CRES 321 ANN TUBING SEAMLESS	
	02151	TUBING TFE HST	
MD127-0048	10101	CRES 321 ANN TUBING SEAMLESS	
	02151	TUBING TFE HST	
MD127-0049	10101	CRES 321 ANN TUBING SEAMLESS	
	02151	TUBING TFE HST	
MD127-0051-000X	10004	AL 2024-T8XXX EXTRUSIONS	
	10277	COATING ANODIC TYPE 2	

MSFC-HDBK-527 REV F ■ 9999942 0007059 0 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD127-0052	10025	AL 6061-T6/62 DRWN SMLESS TUBE	
	10285	CRES PH13-8MO-H1050 BAR FRG	
	05265	CTNG FUSECOTE 879W/1000 EPOXY	
	05015	PRIMER 515-700 SUPER KOROPON	
MD127-0053	10025	AL 6061-T6/62 DRWN SMLESS TUBE	
	10285	CRES PH13-8MO-H1050 BAR FRG	
	00666	CTNG CONVERSION CHROMATE INORG	
	05015	PRIMER 515-700 SUPER KOROPON	
	02151	TUBING TFE HST	
MD127-0054-0001	10025	AL 6061-T6/62 DRWN SMLESS TUBE	
	10285	CRES PH13-8MO-H1050 BAR FRG	
	05265	CTNG FUSECOTE 879/1000 EPOXY	
	05015	PRIMER 515-700 SUPER KOROPON	
MD127-0054-0002	10025	AL 6061-T6/62 DRWN SMLESS TUBE	
	10285	CRES PH13-8MO-H1050 BAR FRG	
	05265	CTNG FUSECOTE 879W/1000 EPOXY	
	05015	PRIMER 515-700 SUPER KOROPON	
MD127-0054-0003	10025	AL 6061-T6/62 DRWN SMLESS TUBE	
	10285	CRES PH13-8MO-H1050 BAR FRG	
	05265	CTNG FUSECOTE 879W/1000 EPOXY	
	05015	PRIMER 515-700 SUPER KOROPON	
MD127-0055-0001	10025	AL 6061-T6/62 DRWN SMLESS TUBE	
	10285	CRES PH13-8MO-H1050 BAR FRG	
	05265	CTNG FUSECOTE 879W/1000 EPOXY	
	05015	PRIMER 515-700 SUPER KOROPON	
MD127-0055-0002	10025	AL 6061-T6/62 DRWN SMLESS TUBE	
	10285	CRES PH13-8MO-H1050 BAR FRG	
	05265	CTNG FUSECOTE 879W/1000 EPOXY	
	05015	PRIMER 515-700 SUPER KOROPON	
MD127-0055-0003	10025	AL 6061-T6/62 DRWN SMLESS TUBE	
	10285	CRES PH13-8MO-11050 BAR FRG	
	05265	CTNG FUSECOTE 879W/1000 EPOXY	
	05015	PRIMER 515-700 SUPER KOROPON	
MD127-0056	10025	AL 6061-T6/62 DRWN SMLESS TUBE	
	10285	CRES PH13-8MO-H1050 BAR FRG	
	00666	CTNG CONVERSION CHROMATE INORG	
	05015	PRIMER 515-700 SUPER KOROPON	
	02151	TUBING TFE HST	
MD127-0059	10087	CRES 301 FUL HD PLT SHT STRIP	
	05272	SEAL SILIC/NOMEX STYLE 160-99	
MD127-0064	10025	AL 6061-T6/62 DRWN SMLESS TUBE	
	10285	CRES PH13-8MO-H1050 BAR FRG	
	00666	CTNG CONVERSION CHROMATE INORG	
	05015	PRIMER 515-700 SUPER KOROPON	
	00016	TEFLON TFE	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD127-0065	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	00666	CTNG CONVERSION CHROMATE INORG	
	90001	SUBSTITUTION INFO. PRESENT	
MD127-0066	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	00666	CTNG CONVERSION CHROMATE INORG	
	90001	SUBSTITUTION INFO. PRESENT	
MD127-0067	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	00666	CTNG CONVERSION CHROMATE INORG	
	90001	SUBSTITUTION INFO. PRESENT	
MD127-0068	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	00666	CTNG CONVERSION CHROMATE INORG	
MD127-0069	10025	AL 6061-T6/62 DRWN SMLESS TUBE	
	10285	CRES PH13-8MO-H1050 BAR FRG	
	00666	CTNG CONVERSION CHROMATE INORG	
	05015	PRIMER 515-700 SUPER KOROPON	
	02151	TUBING TFE HST	
MD127-0070	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	00666	CTNG CONVERSION CHROMATE INORG	
	05135	PRIMER EPOXY/POLYAMIDE	
MD127-0071-0060	10226	CRES 321 ANN TUBING	
	02151	TUBING TFE HST	
MD127-0072	10101	CRES 321 ANN TUBING SEAMLESS	
	02151	TUBING TFE HST	
MD127-0073-0001	10226	CRES 321 ANN TUBING	
	02151	TUBING TFE HST	
MD127-0073-0002	10226	CRES 321 ANN TUBING	
	02151	TUBING TFE HST	
MD127-0074	10101	CRES 321 ANN TUBING SEAMLESS	
	05265	CTNG FUSECOTE 879W/1000 EPOXY	
MD127-0075-1005	05729	CLAMP CUSH SIL/GLASS LAMIN JM	
	10097	CRES 321 ANN SHT PLT STRIP	
MD128-0002	10267	CRES A286 FASTENER MATL ONLY	
	00881	LUBE DRY EVERLUBE 812 (INORG)	
MD128-0003	10267	CRES A286 FASTENER MATL ONLY	
	00881	LUBE DRY EVERLUBE 812 (INORG)	
MD128-0004	10267	CRES A286 FASTENER MATL ONLY	
	00881	LUBE DRY EVERLUBE 812 (INORG)	
MD128-0005	10267	CRES A286 FASTENER MATL ONLY	
	00881	LUBE DRY EVERLUBE 812 (INORG)	

MSFC-HDBK-527 REV F ■ 9999942 0007061 9 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD128-0006	10089	CRES 302 COND B BAR AND WIRE	
MD128-0007	05208	MOLD CPD 4203 TORLON	
MD128-0008-0002	05208	MOLD CPD 4203 TORLON	
MD128-0009	05208	MOLD CPD 4203 TORLON	
MD128-0010-0001	05084	KEL-F UNPLASTICIZED	
MD128-0010-0002	05208	MOLD CPD 4203 TORLON	
MD128-0014	05208	MOLD CPD 4203 TORLON	
MD128-0015	10205	AL 2024-T8XX SHT&PLT(NOT T86X)	
	10036	AL 2219-T8511/6X EXT PRODUCTS	
	10321	BRASS, ALL FORM	
	10277	COATING ANODIC TYPE 2	
	00666	CTNG CONVERSION CHROMATE INORG	
	05201	CTNG POLYU WHITE (17875,37886)	
	10046	PLATING NI ELECTROLESS	
	05015	PRIMER 515-700 SUPER KOROPON	
MD131-6001	00597	LUBE DRY	
	10415	NI INCO 718 ST 1950 BAR & FRG	
	10275	PLATING CHROMIUM (CLASS 2)	
MD131-6002	10011	CRES A286 140 KSI BAR FRG TBNG	
	00597	LUBE DRY	
	10505	NI INCO 718 ST 1750 OR 1950 BR	
	10275	PLATING CHROMIUM (CLASS 2)	
MD131-6003-0028	10416	CRES 17-4PH H1150 BAR ROD FRG	
	30008	CRES 440C RC 58 BAR FRG	
	05053	LUBE LINER KAHR-LON X1200S	
	10275	PLATING CHROMIUM (CLASS 2)	
MD131-6003-0034	10416	CRES 17-4PH H1150 BAR ROD FORG	
	30008	CRES 440C RC 58 BAR FRG	
	05053	LUBE LINER KAHR-LON X1200S	
	10275	PLATING CHROMIUM (CLASS 2)	
MD131-6003-0048	10416	CRES 17-4 PH H1150 BAR ROD FRG	
	30008	CRES 440C RC 58 BAR FRG	
	05053	LUBE LINER KAHR-LON X1200S	
	10275	PLATING CHROMIUM (CLASS 2)	
MD131-6005	10011	CRES A286 140 KSI BAR FRG TBNG	
	00597	LUBE DRY	
	10505	NI INCO 718 ST 1750 OR 1950 BR	
	10275	PLATING CHROMIUM (CLASS 2)	
MD137-0001	10410	AL-BRONZE COMP 630/642 BAR	
MD137-0002	10410	AL-BRONZE COMP 630/642 BAR	

MSFC-HDBK-527 REV F 9999942 0007062 0

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD137-0003	10410	AL-BRONZE COMP 630/642 BAR	
MD137-0004	10257	AL-BRONZE 110KSI BEARING SP BR	
MD137-0005	10257	AL-BRONZE 110KSI BEARING SP BR	
MD137-0006	10399	CRES 17-4PH H1025 BAR FRG RING	
MD137-0007	10399	CRES 17-4PH H1025 BAR FRG RING	
MD137-0008	10399	CRES 17-4PH H1025 BAR FRG RING	
MD137-0009	10415	NI INCO 718 ST 1950 BAR & FRG	
MD137-0010	10415	NI INCO 718 ST 1950 BAR & FRG	
MD137-0011	10415	NI INCO 718 ST 1950 BAR & FRG	
MD137-0012	10508	AL 2024-T851/T8511 BAR	
	10283	COATING ANODIC TYPE 3 (HARD)	
	00666	CTNG CONVERSION CHROMATE INORG	
MD137-0013	02955	LAMIN GLASS/EPOXY	
MD137-0014	10003	AL 2024-T851/T6/T62 BR RD & WR	
	10276	COATING ANODIC TYPE 1	
	00666	CTNG CONVERSION CHROMATE INORG	
MD137-0015	10267	CRES A286 FASTENER MATL ONLY	
MD137-0016	10011	CRES A286 140 KSI BAR FRG TBNG	
	10125	CRES A286 140KSI BAR & FORGING	
MD151-0003	10136	NI INCO X750 ANN SHT & STRIP	
MD151-0004	10136	NI INCO X750 ANN SHT & STRIP	
MD152-0013	10011	CRES A286 140 KSI BAR FRG TBNG	
MD152-0014	10005	AL 2024-T81 TUBE DRAWN SEAMLES	
	10276	COATING ANODIC TYPE 1	
MD152-0016	10004	AL 2024-T8XXX EXTRUSIONS	
	10277	COATING ANODIC TYPE 2	
	05135	PRIMER EPOXY/PLYAMIDE	
MD152-0017	10004	AL 2024-T8XXX EXTRUSIONS	
	10276	COATING ANODIC TYPE 1	
MD152-0018	10004	AL 2024-T8XXX EXTRUSIONS	
	10276	COATING ANODIC TYPE 1	
MD152-0019	02955	LAMIN GLASS/EPOXY	
MD152-0020	00016	TEFLON TFE	

MSFC-HDBK-527 REV F 9999942 0007063 2

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD152-0021	10091	CRES 304 COND B BAR SH FRG WI	
MD152-0022	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	00666	CTNG CONVERSION CHROMATE INORG	
MD153-0014	10424	NI STA INCO 718 FASTENERS ONLY	
MD153-0015	10205	AL 2024-T8XX SHT&PLT(NOT T86X)	
	10277	COATING ANODIC TYPE 2	
MD153-0016-10XX	10252	SHIM STOCK AL (COMP. 1)	
	02860	SHIM STOCK POLYESTER ADHESIVE	
MD153-0016-20XX	10130	SHIM STOCK CRES (COMP. 3)	
	02860	SHIM STOCK POLYESTER ADHESIVE	
MD153-0017	10130	SHIM STOCK CRES (COMP. 3)	
	02860	SHIM STOCK POLYESTER ADHESIVE	
MD153-0018	10088	CRES 301 ANN THRU 1/2 HD PT SH	
MD153-0019-0001	10023	AL 6061-T6/651 RLD BAR SHP ROD	
	10277	COATING ANODIC TYPE 2	
	05201	CTNG POLYU WHITE (17875,37886)	
	05015	PRIMER 515-700 SUPER KOROPON	
MD153-0020-0001	00016	TEFLON TFE	
MD153-1001	10424	NI STA INCO 718 FASTENERS ONLY	
MD153-1002	10424	NI STA INCO 718 FASTENERS ONLY	
MD153-1003	10090	CRES 304 ANN SHT PLT STRIP	
MD153-5001	10424	NI STA INCO 718 FASTENERS ONLY	
MD153-5004	10424	NI STA INCO 718 FASTENERS ONLY	
MD153-5006	10268	CRES 300 SERIES FASTENER MATL	
	10312	PLATING TIN E DEP/HT SOLDER DP	
MD154-0003	05005	RUBBER VITON FLUID RESISTANT	
MD154-0004	10205	AL 2024-T8XX SHT&PLT(NOT T86X)	
MD154-0006	02976	RUBBER SILICONE	
MD154-0007	02976	RUBBER SILICONE	
MD154-0008	02976	RUBBER SILICONE	
MD154-0009	02976	RUBBER SILICONE	
MD154-0010	10046	PLATING NI ELECTROLESS	
	10358	STEEL SAE/AISI 1008-1010	

MSFC-HDBK-527 REV F 9999942 0007064 4

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD161-0001	10514	CRES CABLE 300 SERIES	
MD161-0002-00XX	10022	AL 6061-T6/62/651 SHT & PLT	
	10277	COATING ANODIC TYPE 2	
MD161-0002-10XX	10090	CRES 304 ANN SHT PLT STRIP	
	10097	CRES 321 ANN SHT PLT STRIP	
MD162-0001	10267	CRES A286 FASTENER MATL ONLY	
MD162-0002	10430	CRES 17-4PH H1075 BR (RES 266)	
	10159	CRES 316/316L ANN CSTG INV	
MD171-0029	10366	AL 1100 ANN/5052 ANN SHEET	
	10277	COATING ANODIC TYPE 2	
MD171-0042	10348	AL 11XX ANN FOIL	
	10277	COATING ANODIC TYPE 2	
MD172-0022	05241	TAPE MYLAR/ACRYLIC PS ADHES	
MD172-0024	05241	TAPE MYLAR/ACRYLIC PS ADHES	
MD172-0027	05241	TAPE MYLAR/ACRYLIC PS ADHES	
MD172-0028	05241	TAPE MYLAR/ACRYLIC PS ADHES	
MD175-1002	10366	AL 1100 ANN/5052 ANN SHEET	
	10277	COATING ANODIC TYPE 2	
MD175-50XX	05241	TAPE MYLAR/ACRYLIC PS ADHES	
MD175-5108	05835	STREAMER WARNING MD175-5108	
MD175-9008	05241	TAPE MYLAR/ACRYLIC PS ADHES	
MD175-9011	10348	AL 11XX ANN FOIL	
	10276	COATING ANODIC TYPE 1	
	05173	TAPE 465/467/468 ACRYLIC FILM	
MD175-9017	10348	AL 11XX ANN FOIL	
	10277	COATING ANODIC TYPE 2	
	05173	TAPE 465/467/468 ACRYLIC FILM	
MD175-9018	10348	AL 11XX ANN FOIL	
	10276	COATING ANODIC TYPE 1	
	05401	CTNG POLYU GREY COLOR 36231	
	05173	TAPE 465/467/468 ACRYLIC FILM	
MD181-0057	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	00666	CTNG CONVERSION CHROMATE INORG	
MD193-0006	00339	LEXAN CLEAR POLYCARBON	
MD193-0009	05192	ADHES EA9309 EPOXY	
	00339	LEXAN CLEAR POLYCARBON	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD193-0018	10220	CRES 304 ANN WIRE	
	10140	NI INCO 601 ANN SHT PLT STRIP	
MD193-0019	10140	NI INCO 601 ANN SHT PLT STRIP	
MD193-0020	10318	CRES 304L/316L WIRE/SCRN/CLOTH	
	10140	NI INCO 601 ANN SHT PLT STRIP	
MD193-0021	10140	NI INCO 601 ANN SHT PLT STRIP	
MD195-0001	10023	AL 6061-T6/651 RLD BAR SHP ROD	
	10277	COATING ANODIC TYPE 2	
MD196-0001	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0003	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0004	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0005	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0006	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0007	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0008	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0009	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0010	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0011	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0012	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0013	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0014	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0015	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0016	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0017	05590	LAMIN GLASS/EPOXY CE-9010A	
MD196-0018	99011	SEE FILE FOR MATERIALS	
MD198-0001	10148	SPRING 302 COND B WIRE	
MD261-0001-09XX	03458	RUBBER BUTYL	
MD261-0002-09XX	02966	RUBBER BUTYL	
MD261-0003-09XX	02966	RUBBER BUTYL	

MSFC-HDBK-527 REV F 9999942 0007066 8

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD261-0034-09XX	05395	RUBBER AF-E-411 EPDR	
MD261-0036	00987	RUBBER RTV 577/T12 SILICONE	
MD262-0003-0001	05998	CERAMIC AB312 FABRIC & BRAID	
	05000	PRIMER SS4155 SILANE	
	01039	RUBBER RTV 560 SILICONE	
MD262-0003-0002	05998	CERAMIC AB312 FABRIC & BRAID	
	05000	PRIMER SS4155 SILANE	
	01039	RUBBER RTV 560 SILICONE	
MD262-0003-0003	05998	CERAMIC AB312 FABRIC & BRAID	
	05000	PRIMER SS4155 SILANE	
	01039	RUBBER RTV 560 SILICONE	
MD262-0003-0004	05998	CERAMIC AB312 FABRIC & BRAID	
	05000	PRIMER SS4155 SILANE	
	01039	RUBBER RTV 560 SILICONE	
MD262-0003-0005	05998	CERAMIC AB312 FABRIC & BRAID	
	05000	PRIMER SS4155 SILANE	
	01039	RUBBER RTV 560 SILICONE	
MD262-0003-0006	05998	CERAMIC AB312 FABRIC & BRAID	
	05000	PRIMER SS4155 SILANE	
	01039	RUBBER RTV 560 SILICONE	
MD262-0003-0007	05998	CERAMIC AB312 FABRIC & BRAID	
	05000	PRIMER SS4155 SILANE	
	01039	RUBBER RTV 560 SILICONE	
MD262-0003-0008	05998	CERAMIC AB312 FABRIC & BRAID	
	05000	PRIMER SS4155 SILANE	
	01039	RUBBER RTV 560 SILICONE	
MD262-0003-0009	05998	CERAMIC AB312 FABRIC & BRAID	
	05000	PRIMER SS4155 SILANE	
	01039	RUBBER RTV 560 SILICONE	
MD262-0003-0010	05998	CERAMIC AB312 FABRIC & BRAID	
	05000	PRIMER SS4155 SILANE	
	01039	RUBBER RTV 560 SILICONE	
MD262-0003-0011	05998	CERAMIC AB312 FABRIC & BRAID	
	05000	PRIMER SS4155 SILANE	
	01039	RUBBER RTV 560 SILICONE	
MD262-0003-0012	05998	CERAMIC AB312 FABRIC & BRAID	
	05000	PRIMER SS4155 SILANE	
	01039	RUBBER RTV 560 SILICONE	
MD263-0002	05511	SILICA FUSED 99% SIO2 (INORG)	
MD263-0003	05998	CERAMIC AB312 FABRIC & BRAID	
	06080	MB0115-008/9-MA0609-301 T3 CL2	

MSFC-HDBK-527 REV F ■ 9999942 0007067 T ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD263-0003	05000	PRIMER SS4155 SILANE	
	01039	RUBBER RTV 560 SILICONE	
MD263-0004	05021	INSUL DYNAFLEX ALUMINA SILICA	
MD263-0006	05511	SILICA FUSED 99% SI02 (INORG)	
MD263-0008	05998	CERAMIC AB312 FABRIC & BRAID	
	06080	MB0115-008/9-MA0609-301 T3 CL2	
MD265-0001	10007	AL 2219-T852 FORGING	
	10022	AL 6061-T6/62/651 SHT & PLT	
	10277	COATING ANODIC TYPE 2	
	10514	CRES CABLE 300 SERIES	
MD273-0005	10233	CRES 304L ANN BAR & FRG STK VM	
MD273-0023	10093	CRES 304L COND A & B TUBING	
MD273-0025-00XX	10233	CRES 304L ANN BAR & FRG STK	
MD273-0025-10XX	10103	CRES 21-6-9 ANN SHT PLT STRIP	
MD273-0026-00XX	10196	BRAZE 81 AU 16 CU 2 NI	
MD273-0026-10XX	10198	BRAZE 72 AU 22 NI 6 CR	
MD273-0027-0XXX	10510	CRES 304L/321/347/316 ANN TUB	
MD273-0027-1XXX	10105	CRES 21-6-9 ANN/COLD RED TUBE	
MD273-0028-00XX	10196	BRAZE 81 AU 16 CU 2 NI	
MD273-0028-10XX	10198	BRAZE 72 AU 22 NI 6 CR	
MD273-0029	10233	CRES 304L ANN BAR & FRG STK	
MD273-0030	10233	CRES 304L ANN BAR & FRG STK	
MD273-0031	10233	CRES 304L ANN BAR & FRG STK	
MD273-0032-10XX	10091	CRES 304 COND B BAR SHP FRG	
MD273-0032-20XX	10091	CRES 304 COND B BAR SHP FRG	
	05072	LUBE DRY NA SILICATE BASE INOR	
MD273-0033	10431	CRES 300 SERIES NON-FREE MACH	
	10506	CRES 303/304 BAR AND WIRE	
	10351	CRES 304 ANN BAR SHP FRG WIRE	
	10090	CRES 304 ANN SHT PLT STRIP	
	10370	CRES 316 COND A & B BAR	
	10097	CRES 321 ANN SHT PLT STRIP	
	10514	CRES CABLE 300 SERIES	
MD273-0034	10104	CRES 21-6-9 ANN BAR FRG RINGS	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD273-0035	10104	CRES 21-6-9 ANN BAR FRG RINGS	
MD273-0038	10104	CRES 21-6-9 ANN BAR FRG RINGS	
MD273-0039	10104	CRES 21-6-9 ANN BAR FRG RINGS	
MD275-0002-10XX	10069	TI 6AL 4V STA BAR & FORGING	
MD275-0004	01716	LAMIN GLASS/MELAMINE	
MD275-0005	01716	LAMIN GLASS/MELAMINE	
MD411-4002	10501	CU RODS & SHAPES(MD411-400X)	JUMPER ASSEMBLY
	10223	NI COATED CU/NICKEL WIRE	
	10308	PLATING NICKEL ELECTRODEPOSIT	
	00016	TEFLON TFE	
MD411-4004	10501	CU RODS & SHAPES(MD411-400X)	
	10223	NI COATED CU/NICKEL WIRE	
	10308	PLATING NICKEL ELECTRODEPOSIT	
	00016	TEFLON TFE	
MD411-4005	10022	AL 6061-T6/62/651 SHT & PLT	
	00666	CTNG CONVERSION CHROMATE INORG	
MD411-4006	10312	PLATING TIN E DEP/HT SOLDER DP	
	10149	SPRING BE-CU AT WIRE & STRIP	
MD411-4009	10333	CU SHT PLT BAR ANN	
	10312	PLATING TIN E DEP/HT SOLDER DP	
MD411-4010	06432	FILM KAPTON AL/ORG CTD NM50-13	
	05078	FILM KAPTON GOLDIZED REINFORCE	
	90001	SUBSTITUTION INFO. PRESENT	
	05506	THREAD PBI POLYBENZIMIDAZOLE	
MD411-4011	10501	CU RODS & SHAPES(MD411-400X)	
	10223	NI COATED CU/NICKEL WIRE	
	10308	PLATING NICKEL ELECTRODEPOSIT	
	00016	TEFLON TFE	
MD411-4012	10642	CU NI CLAD	
	10223	NI COATED CU/NICKEL WIRE	
MD411-4013	10638	BE-CU ALLOY STRIP	
	10449	SOLDER 5SB	
MD411-4014	10333	CU SHT PLT BAR ANN	
MD416-0004	10321	BRASS, ALL FORMS	
	10311	PLATING COPPER ELECTRO DEPOSIT	
	10079	SOLDER SN 50/60/62/63	
MD416-0006	10321	BRASS, ALL FORMS	
	10311	PLATING COPPER ELECTRO DEPOSIT	
	10312	PLATING TIN E DEP/HT SOLDER DP	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD416-0008	10321	BRASS, ALL FORMS	
	10686	PLATING 40/60 SN-PB TYPE M-222	
	10311	PLATING COPPER ELECTRO DEPOSIT	
	10312	PLATING TIN E DEP/HT SOLDER DP	
MD416-0010	10321	BRASS, ALL FORMS	
	10311	PLATING COPPER ELECTRO DEPOSIT	
	10079	SOLDER SN 50/60/62/63	
MD416-0011	10321	BRASS, ALL FORMS	
	10686	PLATING 40/60 SN-PB TYPE M-222	
	10311	PLATING COPPER ELECTRO DEPOSIT	
MD416-0012	10321	BRASS, ALL FORMS	
	10311	PLATING COPPER ELECTRO DEPOSIT	
	10312	PLATING TIN E DEP/HT SOLDER DP	
MD416-0014	10321	BRASS, ALL FORMS	
	10311	PLATING COPPER ELECTRO DEPOSIT	
	10312	PLATING TIN E DEP/HT SOLDER DP	
MD416-0019	10333	CU SHT PLT BAR ANN	
	10312	PLATING TIN E DEP/HT SOLDER DP	
MD416-0020	10225	NI 200/201 ANN (ALL FORMS)	
MD416-0021	10333	CU SHT PLT BAR ANN	
	10308	PLATING NICKEL ELECTRODEPOSIT	
MD417-0123	00005	ADHES EA828/VERSAMID 115 EPOSY	
	10321	BRASS, ALL FORM	
	05161	LAMIN GLASS/POLYIMIDE	
	10311	PLATING COPPER ELECTRODEPOSIT	
	10079	SOLDER SN50/60/62-63	
MD417-0124	00005	ADHES EA828/VERSAMID 115 EPOXY	
	05192	ADHES EA9309 EPOXY	
	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	10321	BRASS, ALL FORM	
	00666	CTNG CONVERSION CHROMATE INORG	
	05161	LAMIN GLASS/POLYIMIDE	
	10311	PLATING COPPER ELECTRO DEPOSIT	
	10079	SOLDER SN 50/60/62/63	
MD417-0125	00005	ADHES EA828/VERSAMID 115 EPOXY	
	05192	ADHES EA9309 EPOXY	
	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	10321	BRASS, ALL FORM	
	00666	CTNG CONVERSION CHROMATE INORG	
	05161	LAMIN GLASS/POLYIMIDE	
	10311	PLATING COPPER ELECTRO DEPOSIT	
	10079	SOLDER SN 50/60/62/63	
MD417-0126	00005	ADHES EA828/VERSAMID 115 EPOXY	
	05192	ADHES EA9309 EPOXY	
	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	

MSFC-HDBK-527 REV F ■ 9999942 0007070 T ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD417-0126	10321	BRASS, ALL FORM	
	00666	CTNG CONVERSION CHROMATE INORG	
	05161	LAMIN GLASS/POLYIMIDE	
	10311	PLATING COPPER ELECTRO DEPOSIT	
	10079	SOLDER SN 50/60/62/63	
MD417-0127	00005	ADHES EA828/VERSAMID 115 EPOXY	
	05192	ADHES EA9309 EPOXY	
	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	10321	BRASS, ALL FORM	
	00666	CTNG CONVERSION CHROMATE INORG	
	05161	LAMIN GLASS/POLYIMIDE	
	10311	PLATING COPPER ELECTRO DEPOSIT	
	10079	SOLDER SN 50/60/62/63	
MD417-0128	00005	ADHES EA828/VERSAMID 115 EPOXY	
	05192	ADHES EA9309 EPOXY	
	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	10321	BRASS, ALL FORM	
	00666	CTNG CONVERSION CHROMATE INORG	
	05161	LAMIN GLASS/POLYIMIDE	
	10311	PLATING COPPER ELECTRO DEPOSIT	
	10079	SOLDER SN 50/60/62/63	
MD417-0137-0003	00005	ADHES EA828/VERSAMID 115 EPOXY	
	05192	ADHES EA9309 EPOXY	
	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	10321	BRASS, ALL FORM	
	00666	CTNG CONVERSION CHROMATE INORG	
	05161	LAMIN GLASS/POLYIMIDE	
	10311	PLATING COPPER ELECTRO DEPOSIT	
	10079	SOLDER SN 50/60/62/63	
MD421-0006	01342	FILM KAPTON POLYIMIDE	
MD421-0007	10285	CRES PH13-8MO H1050 BAR FRG	
MD421-0008-0001	05161	LAMIN GLASS/POLYIMIDE	
MD421-0008-0002	05161	LAMIN GLASS/POLYIMIDE	
MD421-0008-0003	05161	LAMIN GLASS/POLYIMIDE	
MD450-0006	10173	WELD WIRE CRES PH13-8	
MD450-0007	10173	WELD WIRE CRES PH13-8	
MD450-0009	10173	WELD WIRE CRES PH13-8	
MD450-0010	10173	WELD WIRE CRES PH13-8	
MD450-0012	10156	CRES 17-4PH 150KSI CSTG INV	
MD450-0013	10156	CRES 17-4PH 150KSI CSTG INV	

MSFC-HDBK-527 REV F 9999942 0007071 1

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MD450-0014-0001	10173	WELD WIRE CRES PH13-8	
MD450-0014-0002	10173	WELD WIRE CRES PH13-8	
MD450-0014-0003	10173	WELD WIRE CRES PH13-8	
MD450-0014-0004	10046	PLATING NI ELECTROLESS	
	10173	WELD WIRE CRES PH13-8	
MD450-0014-0005	10046	PLATING NI ELECTROLESS	
	10173	WELD WIRE CRES PH13-8	
MD450-0014-0006	10046	PLATING NI ELECTROLESS	
	10173	WELD WIRE CRES PH1308	
MD450-0015	10729	TI 6AL-4V INVESTMENT CSTG	
MD450-0016	10729	TI 6AL-4V INVESTMENT CSTG	
MDM-XXPSP	10396	AL A380 CASTING	CONNECTOR, MDM
	10268	CRES 300 SERIES FASTENER MATL	
	10352	CU WIRE GOLD PLATED	
	00070	MOLD CPD FS10 DAP	
	30082	PLATING CADMIUM & CHROMATE	
MDM-XXSSP	10396	AL A380 CASTING	CONNECTOR, MDM
	10268	CRES 300 SERIES FASTENER MATL	
	10352	CU WIRE GOLD PLATED	
	00070	MOLD CPD FS10 DAP	
	30082	PLATING CADMIUM & CHROMATE	
ME 127-0071	30111	AL 2024-T4	CLAMP-P
	05143	SILICONE RUBBER	
ME112-0011-3607	10267	CRES A286	SCREW CAPTIVE
MF1001	10267	CRES A286 FASTENER MATL ONLY	
	00597	LUBE DRY	
MF6001	10267	CRES A286 FASTENER MATL ONLY	
	00597	LUBE DRY	
MK3331	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MK4001	10267	CRES A286 FASTENER MATL ONLY	
	00597	LUBE DRY	
MK4031	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MP54XXXT-XXX	10401	TI 6AL-4V STA BAR FRG	FITTING,DYNATUBE
MR44000N	10384	NI INCO 718 ST/STA BAR	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS 16535-247	10335	AL 2117-T4 ANN ROD&WIRE	RIVET
MS 20426 A	10279	AL 1100	RIVET
MS 20426 AD	10335	AL 2117-T4	RIVET
MS 20426 B	10377	AL 5056	RIVET
MS 20426 D	30099	AL 2017-T4	RIVET
MS 20426 DD	30111	AL 2024-T4	RIVET
MS 21122	10098	CRES 321	CLAMP,LOOP
MS 21266-2N	05353	NYLON PLASTIC	EDGING
MS 24671	10268	CRES 300 SERIES	SCREW
MS 24674	10431	CRES 300 SERIES	SCREW
MS 35219	30112	AL 2024-T4	SCREW
MS 35338-XX	10268	CRES 300 SERIES	
	05559	CTNG PHOSPHATE	
	50124	PLATING CADMIUM	
MS 35649-XX4	20132		NUT
	10268	CRES 300 SERIES	
MS 87033-E2	05241	TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
MS12043-XX	10267	A286 CRES	NUT
	10281	SILVER PLATE	
MS122026	30082	PLATING CADMIUM & CHROMATE	WASHER,LOCK
	30104	STEEL ALLOY RC47-63	
MS122027	30082	PLATING CADMIUM & CHROMATE	WASHER,LOCK
	30104	STEEL ALLOY RC47-63	
MS122028	30082	PLATING CADMIUM & CHROMATE	WASHER,LOCK
	30104	STEEL ALLOY RC47-63	
MS122029	30082	PLATING CADMIUM & CHROMATE	WASHER,LOCK
	30104	STEEL ALLOY RC47-63	
MS122030	30082	PLATING CADMIUM & CHROMATE	WASHER,LOCK
	30104	STEEL ALLOY RC47-63	
MS122031	30082	PLATING CADMIUM & CHROMATE	WASHER,LOCK
	30104	STEEL ALLOY RC47-63	
MS122032	30082	PLATING CADMIUM & CHROMATE	WASHER,LOCK
	30104	STEEL ALLOY RC47-63	

MSFC-HDBK-527 REV F 9999942 0007073 5

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS122033	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122034	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122035	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122036	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122037	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122038	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122039	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122040	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122041	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122042	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122043	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122044	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122045	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122046	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122047	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122048	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122049	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122050	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122051	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0007074 7

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS122052	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122053	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122054	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122055	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122056	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122057	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122058	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122059	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122060	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122061	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122062	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122063	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122064	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122065	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122066	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122067	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122068	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122069	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122070	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK

MSFC-HDBK-527 REV F 9999942 0007075 9

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS122071	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122072	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122073	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122074	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122075	30082 30104	PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	WASHER,LOCK
MS122076	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122077	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122078	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122079	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122080	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122081	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122082	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122083	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122084	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122085	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122086	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122087	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122088	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122089	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122090	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122091	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122092	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122093	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122094	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122095	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS122096	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122097	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122098	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122099	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122100	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122101	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122102	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122103	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122104	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122105	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122106	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122107	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122108	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122109	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122110	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122111	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122112	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122113	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122114	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122115	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122116	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122117	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122118	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122119	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122120	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122121	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122122	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122123	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL

MSFC-HDBK-527 REV F 9999942 0007077 2

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS122124	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122125	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122126	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122127	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122128	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122129	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122130	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122131	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122132	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122133	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122134	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122135	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122136	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122137	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122138	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122139	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122140	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122141	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122142	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122143	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122144	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122145	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122146	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122147	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122148	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122149	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122150	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122151	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS122152	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122153	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122154	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122155	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122156	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122157	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122158	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122159	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122160	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122161	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122162	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122163	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122164	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122165	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122166	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122167	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122168	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122169	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122170	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122171	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122172	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122173	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122174	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122175	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122176	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122177	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122178	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122179	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL

MSFC-HDBK-527 REV F 9999942 0007079 6

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS122180	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122181	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122182	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122183	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122184	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122185	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122186	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122187	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122188	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122189	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122190	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122191	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122192	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122193	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122194	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122195	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122236	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122237	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122238	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122239	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122240	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122241	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122242	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122243	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122244	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122245	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122246	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122247	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS122248	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122249	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122250	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122251	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122252	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122253	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122254	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122255	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122256	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122257	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122258	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122259	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122260	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122261	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122262	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122263	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122264	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122265	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122266	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122267	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122268	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122269	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122270	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122271	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122272	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122273	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122274	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS122275	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS122900	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122901	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122902	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122903	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122904	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122905	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122906	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122907	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122908	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122909	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122910	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122911	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122912	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122913	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122914	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122915	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122916	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122917	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122918	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122919	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122920	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122921	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122922	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122923	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122924	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122925	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122926	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122927	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP

MSFC-HDBK-527 REV F ■ 9999942 0007082 6 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS122928	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122929	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122930	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122931	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122932	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122933	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122934	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122935	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122936	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122937	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122938	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS122939	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS124651	30080	CRES 303 BAR FRG FREE MACHINE	INSERT
MS124652	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124653	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124654	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124655	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124656	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124657	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124658	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124659	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124660	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124661	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124662	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124663	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124664	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124665	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124666	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL

MSFC-HDBK-527 REV F 9999942 0007083 8

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS124667	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124668	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124669	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124670	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124671	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124672	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124673	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124674	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124675	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124676	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124677	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124678	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124679	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124680	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124681	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124682	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124683	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124684	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124685	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124686	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124687	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124688	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124689	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124690	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124691	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124692	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124693	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124694	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL

MSFC-HDBK-527 REV F 9999942 0007084 T

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS124695	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124696	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124697	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124698	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124699	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124700	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124701	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124702	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124703	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124704	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124705	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124706	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124707	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124708	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124709	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124710	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124711	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124712	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124713	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124714	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124715	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124716	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124717	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124718	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124719	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124720	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124721	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124722	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL

MSFC-HDBK-527 REV F 9999942 0007085 1

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS124723	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124724	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124725	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124726	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124727	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124728	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124729	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124730	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124731	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124732	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124733	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124734	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124735	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124736	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124737	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124738	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124739	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124740	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124741	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124742	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124743	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124744	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124745	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124746	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124747	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124748	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124749	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124750	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS124751	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124752	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124753	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124754	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124755	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124756	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124757	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124758	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124759	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124760	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124761	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124762	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124763	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124764	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124765	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124766	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124767	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124768	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124769	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124770	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124771	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124772	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124773	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124774	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124775	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124776	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124777	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124778	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL

MSFC-HDBK-527 REV F 9999942 0007087 5

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS124779	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124780	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124781	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124782	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124783	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124784	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124785	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124786	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124787	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124788	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124789	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124790	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124791	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124792	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124793	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124794	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124795	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124796	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124797	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124798	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124799	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124800	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124801	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124802	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124803	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124804	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124805	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124806	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS124307	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124808	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124809	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS124810	10606	CRES 18-8 (18.5CR-9.2NI)	INSERT,HELICAL
MS14101	10399	CRES 17-4PH H1025 BAR FRG RING	BEARING,PLAIN
	30008	CRES 440C RC 58 BAR FRG	
	05053	LUBE LINER KAHR-LON X1200S	
MS14102	10399	CRES 17-4PH H1025 BAR FRG RING	BEARING,PLAIN
	30008	CRES 440C RC 58 BAR FRG	
	05053	LUBE LINER KAHR-LON X1200S	
MS14103	10399	CRES 17-4PH H1025 BAR FRG RING	BEARING,PLAIN
	30008	CRES 440C RC 58 BAR FRG	
	05053	LUBE LINER KAHR-LON X1200S	
MS14104	10399	CRES 17-4PH H1025 BAR FRG RING	BEARING,PLAIN
	30008	CRES 440C RC 58 BAR FRG	
	05053	LUBE LINER KAHR-LON X1200S	
MS14151-X	10090	CRES 304 ANN SHT PLT STRIP	WASHER,FLAT
MS150451	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150452	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150453	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150454	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150455	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150456	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150457	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150458	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150459	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150460	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150461	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150462	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150463	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150464	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150465	10107	STEEL 52100 RC 55 BAR	BALL,STEEL

MSFC-HDBK-527 REV F 9999942 0007089 9

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS150466	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150467	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150468	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150469	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150470	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150471	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150472	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150473	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150474	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150475	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150476	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150477	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150478	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150479	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150480	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150481	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150482	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150483	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150484	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150485	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150486	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150487	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150488	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150489	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150490	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150491	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150492	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150493	10107	STEEL 52100 RC 55 BAR	BALL,STEEL

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS150494	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150495	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150496	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150497	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150498	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150499	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS150500	10107	STEEL 52100 RC 55 BAR	BALL,STEEL
MS15795	10268	CRES 300 SERIES	WASHER
MS15795-5XX	10333	CU SHT PLT BAR ANN	WASHER,FLAT
MS15795-7XX	30105 10276	AL 2014-T6,2024-T6/T851 BAR COATING ANODIC TYPE 1	WASHER,FLAT
MS15795-8XX	10268	CRES 300 SERIES FASTENER MATL	WASHER,FLAT
MS15795-9XX	10321 05416	BRASS, ALL FORM CTNG CONVERSION BLACK OXIDE	WASHER,FLAT
MS16212-11	10268	CRES 300 SERIES FASTENER MATL	WASHER,FLAT
MS16212-12	10268	CRES 300 SERIES FASTENER MATL	WASHER,FLAT
MS16212-13	10268	CRES 300 SERIES FASTENER MATL	WASHER,FLAT
MS16212-14	10268	CRES 300 SERIES FASTENER MATL	WASHER,FLAT
MS16212-15	10268	CRES 300 SERIES FASTENER MATL	WASHER,FLAT
MS16212-16	10268	CRES 300 SERIES FASTENER MATL	WASHER,FLAT
MS16212-17	10268	CRES 300 SERIES FASTENER MATL	WASHER,FLAT
MS16212-18	10268	CRES 300 SERIES FASTENER MATL	WASHER,FLAT
MS16212-19	10268	CRES 300 SERIES FASTENER MATL	WASHER,FLAT
MS16212-20	10268	CRES 300 SERIES FASTENER MATL	WASHER,FLAT
MS16228-XXC	10268	CRES 300 SERIES FASTENER MATL	NUT,LOCKING
MS16535	99011	SEE FILE FOR MATERIALS	RIVET
MS16555	30114	CRES 410/416	PIN
MS16555-0XX	20132 30104	CTNG BLACK OXIDE (INORGANIC) STEEL ALLOY RC47-63	PIN,STRAIGHT

MSFC-HDBK-527 REV F 9999942 0007091 7

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS16555-1XX	20132 30104	CTNG BLACK OXIDE (INORGANIC) STEEL ALLOY RC47-63	PIN,STRAIGHT
MS16555-6XX	50065	CRES 416 RC36-40	PIN
MS16555-7XX	30114	CRES 410 BAR PLATE	PIN,STRAIGHT
MS16556-41	20132 30104	CTNG BLACK OXIDE (INORGANIC) STEEL ALLOY RC47-63	PIN,STRAIGHT
MS16556-6XX	30114	CRES 410 BAR PLATE	PIN,STRAIGHT
MS16556-7XX	30114	CRES 410 BAR PLATE	PIN,STRAIGHT
MS16562	99011	SEE FILE FOR MATERIALS	PIN,SPRING
MS16562-189	30114	CRES 410 BAR PLATE	PIN
MS16562-190	30114	CRES 410	PIN
MS16562-191	30114	CRES 410/420	PIN
MS16562-192	30114	CRES 410	PIN
MS16562-2XX	30114	CRES 410 OR 420	PIN,SPRING
MS16624-4XXX	10264	SPRING TEMPER 15-7MO RH950	RING,RETAINING
MS16625-4XXX	10264	SPRING TEMPER 15-7MO RH950	RING,RETAINING
MS16625-5XXX	10638	BE-CU ALLOY STRIP	RING,RETAINING
MS16626-4XXX	10264	SPRING TEMPER 15-7MO RH950	RING,RETAINING
MS16626-5XXX	10638		RETAING RING
MS16627-4XXX	10264	SPRING TEMPER 15-7MO RH950	RING,RETAINING
MS16628-4XXX	10264	SPRING TEMPER 15-7MO RH950	RING,RETAINING
MS16628-5XXX	10638	BE-CU ALLOY STRIP	RING,RETAINING
MS16628-5XXX-1	10638 30082	BE-CU ALLOY STRIP PLATING CADMIUM & CHROMATE	RING,RETAINING
MS16629	99011	SEE FILE FOR MATERIALS	RING,RETAINING
MS16629-5XXX	10149	BERYLLIUM COPPER	RING RETAINING
MS16631-5XXX	10149	BE-CU	RING RETAINING
MS16632-4XXX	10264	SPRING TEMPER 15-7MO RH950	RING,RETAINING
MS16633-4XXX	10264	SPRING TEMPER 15-7MO RH950	RING,RETAINING

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS16995-XXX	10268	CRES 300 SERIES FASTENER MATL	SCREW,CAP
MS16996-XXX	10268	CRES 300 SERIES FASTENER MATL	SCREW,CAP
MS17122	10321	BRASS, ALL FORM	TERMINAL, STUD
	10311	PLATING COPPER ELECTRO DEPOSIT	
	10328	PLATING GOLD	
MS171401	30136	CRES 420 BAR PLT SHT STP	PIN
MS171402	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171403	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171404	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171405	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171406	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171407	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171408	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171409	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171410	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171411	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171412	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171413	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171414	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171415	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171416	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171417	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171418	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171419	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171420	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171421	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171422	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171423	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171424	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

MSFC-HDBK-527 REV F 9999942 0007093 0

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171425	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171426	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171427	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171428	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171429	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171430	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171431	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171432	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171433	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171434	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171435	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171436	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171437	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171438	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171439	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171440	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171441	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171442	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171443	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171444	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171445	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171446	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171447	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171448	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171449	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171450	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171451	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171452	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171453	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171454	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171455	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171456	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171457	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171458	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171459	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171460	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171461	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171462	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171463	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171464	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171465	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171466	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171467	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171468	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171469	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171470	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171471	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171472	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171473	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171474	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171475	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171476	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171477	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171478	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171479	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171480	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

MSFC-HDBK-527 REV F 9999942 0007095 4

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171481	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171482	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171483	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171484	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171485	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171486	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171487	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171488	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171489	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171490	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171491	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171492	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171493	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171494	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171495	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171496	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171497	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171498	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171499	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171500	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171501	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171502	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171503	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171504	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171505	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171506	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171507	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171508	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171509	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171510	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171511	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171512	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171513	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171514	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171515	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171516	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171517	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171518	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171519	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171520	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171521	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171522	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171523	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171524	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171525	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171526	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171527	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171528	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171529	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171530	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171531	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171532	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171533	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171534	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171535	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171536	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

MSFC-HDBK-527 REV F 9999942 0007097 8

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171537	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171538	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171539	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171540	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171541	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171542	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171543	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171544	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171545	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171546	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171547	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171548	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171549	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171550	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171551	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171552	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171553	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171554	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171555	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171556	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171557	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171558	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171559	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171560	30136	CRES 420 BAR PLT SHT STP	PIN;SPRING
MS171561	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171562	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171563	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171564	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0007098 T

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171565	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171566	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171567	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171568	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171569	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171570	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171571	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171572	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171573	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171574	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171575	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171576	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171577	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171578	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171579	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171580	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171581	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171582	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171583	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171584	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171585	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171586	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171587	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171588	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171589	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171590	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171591	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171592	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

MSFC-HDBK-527 REV F 9999942 0007099 1

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171593	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171594	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171595	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171596	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171597	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171598	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171599	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS17160	10039 10149	PLATING SILVER SPRING BE-CU AT WIRE & STRIP	CLIP,SPRING
MS171600	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171601	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171602	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171603	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171604	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171605	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171606	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171607	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171608	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171609	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171610	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171611	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171612	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171613	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171614	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171615	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171616	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171617	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171618	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0007100 4

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171619	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171620	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171621	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171622	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171623	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171624	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171625	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171626	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171627	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171628	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171629	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171630	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171631	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171632	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171633	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171634	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171635	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171636	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171637	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171638	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171639	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171640	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171641	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171642	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171643	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171644	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171645	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171646	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171647	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171648	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171649	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171650	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171651	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171652	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171653	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171654	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171655	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171656	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171657	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171658	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171659	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171660	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171661	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171662	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171663	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171664	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171665	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171666	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171667	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171668	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171669	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171670	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171671	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171672	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171673	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
71674	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171675	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171676	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171677	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171678	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171679	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171680	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171681	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171682	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171683	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171684	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171685	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171686	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171687	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171688	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171689	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171690	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171691	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171692	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171693	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171694	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171695	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171696	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171697	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171698	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171699	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171700	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171701	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171702	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171703	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171704	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171705	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171706	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171707	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171708	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171709	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171710	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171711	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171712	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171713	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171714	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171715	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171716	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171717	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171718	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171719	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171720	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171721	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171722	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171723	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171724	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171725	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171726	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171727	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171728	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171729	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171730	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171731	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171732	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171733	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171734	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171735	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171736	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171737	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171738	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171739	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171740	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171741	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171742	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171743	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171744	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171745	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171746	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171747	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171748	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171749	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171750	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171751	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171752	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171753	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171754	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171755	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171756	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171757	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171758	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

MSFC-HDBK-527 REV F 9999942 0007105 3

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171759	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171760	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171761	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171762	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171763	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171764	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171765	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171766	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171767	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171768	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171769	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171770	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171771	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171772	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171773	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171774	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171775	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171776	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171777	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171778	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171779	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171780	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171781	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171782	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171783	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171784	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171785	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171786	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171787	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171788	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171789	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171790	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171791	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171792	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171793	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171794	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171795	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171796	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171797	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171798	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171799	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171800	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171801	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171802	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171803	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171804	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171805	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171806	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171807	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171808	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171809	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171810	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171811	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171812	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171813	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171814	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

MSFC-HDBK-527 REV F 9999942 0007107 7

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171815	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171816	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171817	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171818	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171819	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171820	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171821	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171822	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171823	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171824	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171825	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171826	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171827	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171828	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171829	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171830	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171831	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171832	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171833	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171834	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171835	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171836	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171837	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171838	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171839	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171840	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171841	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171842	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171843	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171844	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171845	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171846	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171847	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171848	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171849	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171850	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171851	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171852	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171853	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171854	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171855	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171856	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171857	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171858	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171859	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171860	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171861	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171862	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171863	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171864	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171865	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171866	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171867	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171868	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171869	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171870	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

MSFC-HDBK-527 REV F 9999942 0007109 0

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171871	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171872	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171873	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171874	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171875	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171876	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171877	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171878	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171879	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171880	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171881	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171882	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171883	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171884	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171885	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171886	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171887	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171888	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171889	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171890	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171891	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171892	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171893	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171894	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171895	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171896	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171897	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171898	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS171899	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS171900	30136	CRES 420 BAR PLT SHT STP	PIN,SPRING
MS17830-XXC	10268	CRES 300 SERIES FASTENER MATL	NUT,LOCKING
MS17985C	30099	AL 2017 ALL TEMPERS	PIN,QUICK RELEAS
	10003	AL 2024-T851/T6/T62 BR RD & WR	
	10636	AL 380 CASTING	
	10024	AL 6061-T6/T6511 EXT BR SHP TB	
	30124	CRES 17-4PH H900/15-7MO TH1050	
	10516	CRES 17-7PH COND C/302 COND B	
	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	10148	SPRING 302 COND B WIRE	
MS18034	05353	NYLON PLASTIC	STRAP,CABLE
MS18064	10268	CRES 300 SERIES FASTENER MATL	SETSCREW,SELF LK
	30080	CRES 303 FREE MACHINING	
	00019	NYLON PLASTIC	
MS18066	10431	CRES 300 SERIES NON-FREE MACH	SETSCREW,SELF LK
	30080	CRES 303 FREE MACHINING	
	00019	NYLON PLASTIC	
MS18068	10268	CRES 300 SERIES FASTENER MATL	SETSCREW,SELF LK
	30080	CRES 303 FREE MACHINING	
	00019	NYLON PLASTIC	
MS18212-XXX	05353	NYLON PLASTIC	SCREW,PLASTIC
MS19060	30002	CRES 440A,440B,440C BAR	BALL BEARING
MS19060-1	50064	CRES 440C	BALL BEARING
MS19069	30087	STEEL 8735 SHEET	WASHER,KEY,RETNG
MS20001-XX	30071	AL 2024-T4	HINGE,BUTT
	00666	CTNG CONVERSION CHROMATE INORG	
MS20001P	30071	AL 2024-T4	HINGE,BUTT
	10277	COATING ANODIC TYPE 2	
	00666	CTNG CONVERSION CHROMATE INORG	
MS20002	30082	PLATING CADMIUM & CHROMATE	WASHER,PLAIN
	10108	STEEL 4130 125-180 KSI SHT PLT	
MS20230AXX	10022	AL 6061-T6/62/651 SHT & PLT	GROMMET
	10277	COATING ANODIC TYPE 2	
MS20230BXX	10321	BRASS, ALL FORM	GROMMET
MS20230GAXX	10022	AL 6061-T6/62/651 SHT & PLT	GROMMET
	10277	COATING ANODIC TYPE 2	

MSFC-HDBK-527 REV F ■ 9999942 0007111 9 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS20230WAXX	10022	AL 6061-T6/62/651 SHT & PLT	GROMMET
	10277	COATING ANODIC TYPE 2	
MS20253-X	10391	CRES 302/304/316 SHT PLT WIRE	PIN, HINGE
MS20253PX	10391	CRES 302/304/316 SHT PLT WIRE	PIN, HINGE
	30082	PLATING CADMIUM & CHROMATE	
MS20257-CX	10268	CRES 300 SERIES FASTENER MATL	HINGE
MS20257-HPX	10503	AL 5052-H32/H34/H36 SHT & PLT	HINGE
	10277	COATING ANODIC TYPE 2	
MS20257-PX	10503	AL 5052-H32/H34/H36 SHT & PLT	HINGE
	10277	COATING ANODIC TYPE 2	
	10391	CRES 302/304/316 SHT PLT WIRE	
	30082	PLATING CADMIUM & CHROMATE	
MS20341-XXC	10431	CRES 300 SERIES NON-FREE MACH	NUT,PLAIN,HEX
MS20392-XXCXX	30082	PLATING CADMIUM & CHROMATE	PIN,STRAIGHT
	30104	STEEL ALLOY RC47-63	
MS20426A	10217	AL 1100 WIRE	RIVET,SOLID
MS20426AD	10335	AL 2117-T4 ANN WIRE (RIVETS)	RIVET,SOLID
	10277	COATING ANODIC TYPE 2	
	00666	CTNG CONVERSION CHROMATE INORG	
MS20426ADK	10335	AL 2117-T4 ANN ROD&WIRE	RIVET
MS20426B	10443	AL 5056-0/H32 ROD & WIRE	RIVET,SOLID
	10277	COATING ANODIC TYPE 2	
	00666	CTNG CONVERSION CHROMATE INORG	
MS20426BX	10033	AL 5052-H191 FOIL	RIVET
MS20426DDX-XX	30108	AL 2024-T3/T4 FASTENERS ONLY	RIVET,SOLID
	10277	COATING ANODIC TYPE 2	
MS20427C	10439	CU WIRE (RIVETS)	RIVET,SOLID
MS20427F	10431	CRES 300 SERIES NON-FREE MACH	RIVET,SOLID
MS20427M	10222	MONEL 400/405 ALL FORMS	RIVET,SOLID
MS20470A	10217	AL 1100 WIRE	RIVET,SOLID
MS20470AD	10335	AL 2117-T4 ANN WIRE (RIVETS)	RIVET,SOLID
	10277	COATING ANODIC TYPE 2	
	00666	CTNG CONVERSION CHROMATE INORG	
MS20470B	10443	AL 5056-0/H32 ROD & WIRE	RIVET,SOLID
	10277	COATING ANODIC TYPE 2	
	00666	CTNG CONVERSION CHROMATE	

MSFC-HDBK-527 REV F 9999942 0007112 0

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS20470DDX-XX	30198	AL 2024-T3/T4 FASTENERS ONLY	RIVET,SOLID
	10277	COATING ANODIC TYPE 2	
	00666	CTNG CONVERSION CHROMATE	
MS20470DX-XX	30099	AL 2017 ALL TEMPERS	RIVET,SOLID
	10277	COATING ANODIC TYPE 2	
	00666	CTNG CONVERSION CHROMATE	
MS20500	10267	CRES A286 FASTENER MATL ONLY	NUT,SELF LOCKING
	10281	PLATING SILVER,FASTENERS ONLY	
MS20600ADXWXX	10335	AL 2117-T4 ANN WIRE (RIVETS)	RIVET,BLIND
	10277	COATING ANODIC TYPE 2	
	00666	CTNG CONVERSION CHROMATE	
MS20601ADXWXX	10335	AL 2117-T4 ANN WIRE (RIVETS)	RIVET,BLIND
	10277	COATING ANODIC TYPE 2	
	00666	CTNG CONVERSION CHROMATE	
MS20604ADXWXX	10335	AL 2117-T4 ANN WIRE (RIVETS)	RIVET,BLIND
	10277	COATING ANODIC TYPE 2	
	00666	CTNG CONVERSION CHROMATE	
MS20604BXWXX	10443	AL 5056-0/H32 ROD & WIRE	RIVET,BLIND
	10277	COATING ANODIC TYPE 2	
	00666	CTNG CONVERSION CHROMATE	
MS20604MLXWXX	10222	MONEL 400/405 ALL FORMS	RIVET,BLIND
	10281	PLATING SILVER,FASTENERS ONLY	
MS20605ADX	10335	AL 2117-T4 ANN WIRE (RIVETS)	RIVET,BLIND
	10277	COATING ANODIC TYPE 2	
	00666	CTNG CONVERSION CHROMATE INORG	
MS20605ADXC	10335	AL 2117-T4 ANN ROD&WIRE	RIVET
MS20605MX	10222	MONEL 400/405 ALL FORMS	RIVET,BLIND
MS20613-XXCXX	10268	CRES 300 SERIES FASTENER MATL	RIVET,SOLID
	30080	CRES 303 FREE MACHINING	
MS20613-XXPXX	50124	PLATING CADMIUM	RIVET,SOLID
	10358	STEEL SAE 1010	
MS20615-XCU	10439	CU WIRE (RIVETS)	RIVET,SOLID
MS20615-XM	10222	MONEL 400/405 ALL FORMS	RIVET,SOLID
MS20615-XMPX	10222	MONEL 400/405 ALL FORMS	RIVET,SOLID
	30082	PLATING CADMIUM & CHROMATE	
MS20658-X	10512	CRES 303/305 BAR	TERMINAL,WIRE
MS20659	10248	BRAZE CU FLAT RODS & SHAPES	TERMINAL,LUG
	10312	PLATING TIN E DEP/HT SOLDER DP	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS20659-138	50114	CU UNINSULATED	TERMINAL
MS20664CX	10512	CRES 303/305 BAR	BALL END,WIRE
MS20667-XX	10512	CRES 303/305 BAR	TERMINAL,WIRE
MS20668-XX	30080	CRES 303 FREE MACHINING	TERMINAL,WIRE
	10336	CRES 305 ANN BAR	
MS20813-1	10321	BRASS, ALL FORM	CAP,AIR VALVE
	20224	LACQUER YELLOW (MS20813)	
	05345	RUBBER NITRILE	
MS20819-XXJ	10351	CRES 304 ANN BAR SHP FRG WIRE	SLEEVE,TUBE
MS20819-XXK	10370	CRES 316 COND A & B BAR	SLEEVE,TUBE
MS20826-XD	10003	AL 6061/T6	TEE
	10277	ANODIC CTNG T2	
MS20913-XXJ	10351	CRES 304 ANN BAR SHP FRG WIRE	PLUG,PIPE
MS20995	10391	CRES 302/304	WIRE
MS20995AB	10443	AL 5056-0/H32 ROD & WIRE	WIRE,LOCK
	10276	COATING ANODIC TYPE 1	
	10277	COATING ANODIC TYPE 2	
MS20995CXX	10391	CRES 302/304/316 SHT PLT WIRE	WIRE,LOCK
MS20995NCXX	10222	MONEL 400/405 ALL FORMS	WIRE,LOCK
MS20995NXX	10009	NI-CR-FE WIRE ANN (INCO 600)	WIRE,LOCK
MS21006-XX	10289	321/347 CRES	LOOP CLAMP
MS21043-3	10267	CRES A286 FASTENER MATL SH	NUT SELF-LOCKING
	10281	PLATING SILVER	
MS21043-XX	10267	CRES A286 FASTENER MATL ONLY	F LOCKING
	10281	PLATING SILVER,FASTENERS ONLY	
MS210 4CXX	05168	CETYL ALCOHOL 96 PERCENT	NUT,SELF LOCKING
	10267	CRES A286 FASTENER MATL ONLY	
	00019	NYLON PLASTIC	
MS21044DXX	30112	AL 2024-T3/T4 PLATE BAR TUBE	NUT,SELF LOCKING
	05168	CETYL ALCOHOL 96 PERCENT	
	10276	COATING ANODIC TYPE 1	
	00019	NYLON PLASTIC	
MS21044NXX	05168	CETYL ALCOHOL 96 PERCENT	NUT,SELF LOCKING
	00019	NYLON PLASTIC	
	50124	PLATING CADMIUM	
	30130	STEEL LOW ALLOY 17-22A	

MSFC-HDBK-527 REV F ■ 9999942 0007114 4 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS21045-XX	50124 30130	PLATING CADMIUM STEEL LOW ALLOY 17-22A	NUT,SELF LOCKING
MS21045CXX	10431 05723	CRES 300 SERIES NON-FREE MACH LUBE DRY	NUT,SELF LOCKING
MS21046CXX	10267 00597	CRES A286 FASTENER MATL ONLY LUBE DRY	NUT,SELF LOCKING
MS21048-XXX	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENERS ONLY	NUT,SELF LOCKING
MS21048LXXX	10267 05723	CRES A286 FASTENER MATL ONLY LUBE DRY	NUT,SELF LOCKING
MS21052-XXX	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENERS ONLY	NUT,SELF LOCKING
MS21052LXXX	10267 05723	CRES A286 FASTENER MATL ONLY LUBE DRY	NUT,SELF LOCKING
MS21056-XXX	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENERS ONLY	NUT PLATE, SF LK
MS21057-XXX	50124 30130	PLATING CADMIUM STEEL LOW ALLOY 17-22A	NUT PLATE, SF LK
MS21057LXXX	00597 50124 30130	LUBE DRY PLATING CADMIUM STEEL LOW ALLOY 17-22A	NUT PLATE, SF LK
MS21058-XXX	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENERS ONLY	NUT PLATE, SF LK
MS21058LXXX	10267 00597	CRES A286 FASTENER MATL ONLY LUBE DRY	NUT PLATE, SF LK
MS21059-XXX	50124 30130	PLATING CADMIUM STEEL LOW ALLOY 17-22A	NUT PLATE, SF LK
MS21059LXXX	00597 50124 30130	LUBE DRY PLATING CADMIUM STEEL LOW ALLOY 17-22A	NUT PLATE, SF LK
MS21060-XXX	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENERS ONLY	NUT PLATE, SF LK
MS21060LXXX	10267 00597	CRES A286 FASTENER MATL ONLY LUBE DRY	NUT PLATE, SF LK
MS21062-XXX	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENERS ONLY	NUT PLATE, SF LK
MS21062LXX	10267 00597	CRES A286 FASTENER MATL ONLY LUBE DRY	NUT PLATE, SF LK

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS21063-X-XX	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	NUT,CHANNEL
	30082	PLATING CADMIUM & CHROMATE	
	10358	STEEL SAE/AISI 1008-1010	
MS21063LX-XX	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	NUT, CHANNEL
	05520	LUBE DRY TIO LUBE 460	
	30082	PLATING CADMIUM & CHROMATE	
	10358	STEEL SAE/AISI 1008-1010	
MS21068-X-XX	10268	CRES 300 SERIES FASTENER MATL	NUT,CHANNEL
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
MS21068LX-XX	10268	CRES 300 SERIES FASTENER ONLY	NUT,CHANNEL
	10267	CRES A286 FASTENER MATL ONLY	
	00597	LUBE DRY	
	10281	PLATING SILVER,FASTENERS ONLY	
MS21070-XXX	10267	CRES A286 FASTENER MATL ONLY	NUT PLATE, SF LK
	10281	PLATING SILVER,FASTENERS ONLY	
MS21070LXXX	10267	CRES A286 FASTENER MATL ONLY	NUT PLATE, SF LK
	00597	LUBE DRY	
MS21072-XXX	10267	CRES A286 FASTENER MATL ONLY	NUT PLATE, SF LK
	10281	PLATING SILVER,FASTENERS ONLY	
MS21072LXX	10267	CRES A286 FASTENER MATL ONLY	NUT PLATE, SF LK
	05723	LUBE DRY	
MS21074-XXX	10267	CRES A286 FASTENER MATL ONLY	NUT PLATE, SF LK
	10281	PLATING SILVER,FASTENERS ONLY	
MS21076-XX	10267	AS86 CRES	NUT SELF LOCKING
	10267	AS86 CRES	
	10267	AS86 CRES	
	10281	SILVER PLATE	
MS21076-XXX	10267	CRES A286 FASTENER MATL ONLY	NUT PLATE, SF LK
	10281	PLATING SILVER,FASTENERS ONLY	
MS21076LXXX	10267	CRES A286 FASTENER MATL ONLY	NUT PLATE, SF LK
	05723	LUBE DRY	
MS21083NXX	00019	NYLON PLASTIC	NUT,SELF LOCKING
	30082	PLATING CADMIUM & CHROMATE	
	10515	STEEL 1055-1090 LOW CARBON	
MS21087-XXX	10267	CRES A286 FASTENER MATL ONLY	NUT PLATE, SF LK
	10281	PLATING SILVER,FASTENERS ONLY	
MS21095-XXXX	10268	CRES 300 SERIES FASTENER MATL	BOLT,SELF LOCKNG
MS21106-XX	10390	CRES 321/347 ANN BR,PLT,TB	CLAMP,LOOP
	10289	CRES 321/347 ANN SHT STDS	

MSFC-HDBK-527 REV F 9999942 0007116 8

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS21122-XX	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	CLAMP,LOOP,CUSH
	00016	TEFLON TFE	
MS21122CXX	10289	CRES 321/347 ANN SHT STDS	CLAMP,LOOP,CUSH
	00016	TEFLON TFE	
MS21140-XXXX	10011	CRES A286 140 KSI BAR FRG TBNG	FASTENER,BLIND
	00597	LUBE DRY	
MS21140-XXXXP	10011	CRES A286 140 KSI BAR FRG TBNG	FASTENER,BLIND
	00597	LUBE DRY	
	30082	PLATING CADMIUM & CHROMATE	
MS21141-XXXX	10011	CRES A286 140 KSI BAR FRG TBNG	FASTENER,BLIND
	00597	LUBE DRY	
MS21141-XXXXP	10011	CRES A286 140 KSI BAR FRG TBNG	FASTENER,BLIND
	00597	LUBE DRY	
	30082	PLATING CADMIUM & CHROMATE	
MS21150	10087	CRES 301 FUL HD PLT SHT STRIP	BEARING,BALL
	05641	LUBE, HYDROCARBON, GREASE	
	30082	PLATING CADMIUM & CHROMATE	
	10109	STEEL 4130 125-180 KSI BAR FRG	
	10107	STEEL 52100 RC 55 BAR	
	05501	TFE/15% GLASS	
MS21206-XXX	30082	PLATING CADMIUM & CHROMATE	WASHER
	10108	STEEL 4130 125-180 KSI BAR FRG	
MS21208	10391	CRES 302/304/316 SHT PLT WIRE	INSERT,SCREW THD
MS21209	10506	CRES 303/304 BAR AND WIRE	INSERT
	00597	LUBE DRY	
MS21209F1-15	10506	CRES 304	INSERT
MS21209XXXXX	10506	CRES 303/304 BAR AND WIRE	INSERT,SCREW THD
MS21209XXXXXL	00597	LUBE DRY	INSERT,SCREW THD
	10645	SPRING 304 WIRE FULL HARD	
MS21209XXXXXP	50124	PLATING CADMIUM	INSERT,SCREW THD
	10645	SPRING 304 WIRE FULL HARD	
MS21241-XXCXX	30114	CRES 410 BAR PLATE	BEARING,SLEEVE
	00016	TEFLON TFE	
MS21250XXXX	50124	PLATING CADMIUM	BOLT, 12 POINT
	50123	STEEL 4XXX/8XXX	
MS21266-XN	00019	NYLON PLASTIC	GROMMET,PLASTIC
MS21266-XT	00016	TEFLON TFE	GROMMET,PLASTIC

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS21279	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
MS21280	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
MS21286	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
MS21288	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
MS21288-021	10267	CRES A286	BOLT
MS21288-066	10267	CRES A286	BOLT
MS21318	30082 10359	PLATING CADMIUM & CHROMATE STEEL AISI/SAE 1010 TO 1040	SCREW,DRIVE
MS21340-0X	10268	CRES 300 SERIES FASTENER MATL	NUT,PLAIN
MS21916J	10351	CRES 304 ANN BAR SHP FRG WIRE	REDUCER,TUBE
MS21919DGXX	10408 05336	AL 2024T3/T4X/T6X/T8XX CLD SHT CLAMP CUSHION MS21919WDG NEOPR	CLAMP,CUSHIONED
MS21919GXX	05336 30082 10358	CLAMP CUSHION MS21919WDG NEOPR PLATING CADMIUM & CHROMATE STEEL SAE/AISI 1008-1010	CLAMP,CUSHIONED
MS21919WGXX	05336 30082 10358	CLAMP CUSHION MS21919WDG NEOPR PLATING CADMIUM & CHROMATE STEEL SAE/AISI 1008-1010	CLAMP,CUSHIONED
MS21921-XXK	10370	CRES 316 COND A & B BAR	NUT,FLARELESS
MS21980	10321 10312	BRASS, ALL FORM PLATING TIN E DEP/HT SOLDER DP	FERRULE,OUTER
MS21981	10321 10312	BRASS, ALL FORM PLATING TIN E DEP/HT SOLDER DP	FERRULE,INNER
MS24390JXX	10351	CRES 304 ANN BAR SHP FRG WIRE	TEE,FLARED TUBE
MS24391C	10431	CRES 300 SERIES NON-FREE MACH	PLUG-BLEEDER
MS24391D	10003 10277	AL 2024-T851/T6/T62 BR RD WR COATING ANODIC TYPE 2	PLUG-BLEEDER
MS24391J	10351	CRES 304 ANN BAR SHP FRG WIRE	PLUG-BLEEDER
MS24391K	10370	CRES 316 COND A & B BAR	PLUG-BLEEDER
MS24391S	10100	CRES 347 ANN BAR SHP FRG WIRE	PLUG-BLEEDER
MS24392D	30195 10277	AL 2014-T6,2024T6/T851 BAR COATING ANODIC TYPE 2	NIPPLE,TUBE
1392J	10351	CRES 304 ANN BAR SHP FRG WIRE	NIPPLE,TUBE

MSFC-HDBK-527 REV F 9999942 0007118 1

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS24392K	10370	CRES 316 COND A & B BAR	NIPPLE,TUBE
MS24393-XX	50124 50135	PLATING CADMIUM STEEL 4XXX/8XXX 125 KSI UTS	NIPPLE,TUBE
MS24393D	30105 10277	AL 2014-T6,2024-T6/T851 BAR COATING ANODIC TYPE 2	NIPPLE,TUBE
MS24393J	10351	CRES 304 ANN BAR SHP FRG WIRE	NIPPLE,TUBE
MS24394D	30105 10277	AL 2014-T6,2024-T6/T851 BAR COATING ANODIC TYPE 2	ELBOW,TUBE
MS24394J	10351	CRES 304 ANN BAR SHP FRG WIRE	ELBOW,TUBE
MS24395J	10351	CRES 304 ANN BAR SHP FRG WIRE	TEE,TUBE
MS24396JXX	10351	CRES 304 ANN BAR SHP FRG WIRE	ELBOW,TUBE
MS24397J	10351	CRES 304 ANN BAR SHP FRG WIRE	REDUCER,BOSS
MS24397S	10100	CRES 347 ANN BAR SHP FRG WIRE	REDUCER,BOSS
MS24398J	10351	CRES 304 ANN BAR SHP FRG WIRE	ADAPTER,STRAIGHT
MS24399J	10351	CRES 304 ANN BAR SHP FRG WIRE	REDUCER,TUBE
MS24401J	10351	CRES 304 ANN BAR SHP FRG WIRE	ELBOW,TUBE
MS24402J	10351	CRES 304 ANN BAR SHP FRG WIRE	TEE,TUBE
MS24403JXX	10351	CRES 304 ANN BAR SHP FRG WIRE	CROSS,TUBE
MS24404D	30105 10277	AL 2014-T6,2024T6/T851 BAR COATING ANODIC TYPE 2	PLUG,TUBE
MS24404J	10351	CRES 304 ANN BAR SHP FRG WIRE	PLUG,TUBE
MS24404K	10370	CRES 316 COND A & B BAR	PLUG,TUBE
MS24405JXX	10351	CRES 304 ANN BAR SHP FRG WIRE	ADAPTER,TUBE
MS24487D	30105 10277	AL 2014-T6,2024-T6/T851 BAR COATING ANODIC TYPE 2	NIPPLE,TUBE
MS24585-1XXX	30082 10232	PLATING CADMIUM & CHROMATE SPRING STEEL MUSIC WIRE	SPRING,HELICAL
MS24585-CXXX	10391	CRES 302/304/316 SHT PLT WIRE	SPRING,HELICAL
MS24586	10220 10148	CRES 304 ANN WIRE SPRING 302 COND B WIRE	SPRING,HELICAL
MS24622	30114	CRES 410 BAR PLATE	SCREW,TAPPING

MSFC-HDBK-527 REV F 9999942 0007119 3

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS24630	30149	CRES 400 SERIES	SCREW,TAPPING
MS24665	99011	SEE FILE FOR MATERIALS	PIN,COTTER
MS24673	10268	CRES 300 SERIES FASTENER MATL	SCREW,CAP
MS24674	99011	SEE FILE FOR MATERIALS	SCREW,CAP
MS24680	99011	SEE FILE FOR MATERIALS	NUT,PLAIN,CAP
MS24690	05490	INK 977-9	PACKING,PREFORM
	05499	RUBBER NITRILE	
MS24693-C	10268	CRES 300 SERIES FASTENER MATL	SCREW,MACHINE
	30080	CRES 303 FREE MACHINING	
MS24693-NB	10321	BRASS, ALL FORM	SCREW,MACHINE
	10308	PLATING NICKEL ELECTRODEPOSIT	
MS24694-C	10268	CRES 300 SERIES FASTENER MATL	SCREW,MACHINE
MS25036-XXX	50114	CU TERMINAL LUG & SPL (TINNED)	TERMINAL,LUG
	20017	TUBING POLYOLEFIN HST CL2	
MS25082-BXX	10321	BRASS, ALL FORM	NUT,PLAIN,HEX
	05416	CTNG CONVERSION BL OXIDE(INOR)	
MS25082-CXX	10268	CRES 300 SERIES FASTENER MATL	NUT,PLAIN,HEX
MS25082-XX	30082	PLATING CADMIUM & CHROMATE	NUT,PLAIN,HEX
	10515	STEEL 1055-1090 LOW CARBON	
MS25083-2	10501	CU RODS & SHAPES	JUMPER ASSEMBLY
	10330	CU WIRE TIN PLATED	
	10312	PLATING TIN E DEP/HT SOLDER DP	
MS25083-7	10385	AL 3003-0 BAR	JUMPER ASSEMBLY
	10443	AL 5056-0/H32 ROD & WIRE	
	00666	CTNG CONVERSION CHROMATE INORG	
	20022	TUBING RNF - 100 POLYOLEFIN	
MS25226-XX	10333	CU SHT PLT BAR ANN	LINK,TERMINAL
	30082	PLATING CADMIUM & CHROMATE	
MS25226-XXN	10333	CU SHT PLT BAR ANN	LINK,TERMINAL
	10308	PLATING NICKEL ELECTRODEPOSIT	
MS25226-XXS	10333	CU SHT PLT BAR ANN	LINK,TERMINAL
	10039	PLATING SILVER	
MS25226-XXT	10333	CU SHT PLT BAR ANN	LINK,TERMINAL
	10312	PLATING TIN E DEP/HT SOLDER DP	
MS25281	99010	NOT TO BE USED ON SHUTTLE	CLAMP,LOOP

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS27039CXX	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
MS27111	30082	PLATING CADMIUM & CHROMATE	WASHER,KEY,FLAT
	10359	STEEL AISI/SAE 1010 TO 1040	
MS27196	10294	CRES 302 ANN THRU 1/2 HD PT SH	GASKET,RUBBER
	05005	RUBBER VITON FLUID RESISTANT	
MS27212-1-XX	10512	CRES 303/305 BAR	TERMINAL BD ASSY
	05196	MOLD CPD DAP/GLASS FIL GDI-30F	
MS27212-2-XX	10512	CRES 303/305 BAR	TERMINAL BD ASSY
	05196	MOLD CPD DAP/GLASS FIL GDI-30F	
MS27363	99011	SEE FILE FOR MATERIALS	HOSE ASSEMBLY
MS27436T	30080	CRES 303 FREE MACHINING	VALVE,SPECIAL
	10312	PLATING TIN E DEP/HT SOLDER DP	
MS27467	99011	SEE FILE FOR MATERIALS	CONNECTOR,PLUG
MS27473	99011	SEE FILE FOR MATERIALS	CONNECTOR,PLUG
MS27474	99011	SEE FILE FOR MATERIALS	CONNECTOR,RECEPT
MS27476	99011	SEE FILE FOR MATERIALS	CONNECTOR,RECEPT
MS27478	99011	SEE FILE FOR MATERIALS	CONNECTOR,RECEPT
MS27488	00016	TEFLON TFE	PLUG,GROMMET
	00649	TEFLON TFE	
MS27494	10352	CU WIRE GOLD PLTD (ELEC CONN)	CONTACT,ELEC,PIN
MS27497	99011	SEE FILE FOR MATERIALS	CONNECTOR,RECEPT
MS27503	99011	SEE FILE FOR MATERIALS	CONNECTOR,RECEPT
MS27511AXXC	30112	AL 2024-T3/T4 PLATE BAR TUBE	CAP,PROTECTIVE
	10431	CRES 300 SERIES NON-FREE MACH	
	30080	CRES 303 FREE MACHINING	
	30082	PLATING CADMIUM & CHROMATE	
	10308	PLATING NICKEL ELECTRODEPOSIT	
	02976	RUBBER SILICONE	
MS27511CXXC	30112	AL 2024-T3/T4 PLATE BAR TUBE	CAP,PROTECTIVE
	10283	COATING ANODIC TYPE 3 (HARD)	
	10431	CRES 300 SERIES NON-FREE MACH	
	30080	CRES 303 FREE MACHINING	
	02976	RUBBER SILICONE	
MS27512-XXE	30080	CRES 303 FREE MACHINING	NUT,HEX
MS27595	00016	TEFLON TFE	RETAINER

MSFC-HDBK-527 REV F 9999942 0007121 1

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F.

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS27641	05641	LUBE HYDROCARBON GREASE	BEARING,BALL
	30082	PLATING CADMIUM & CHROMATE	
	10107	STEEL 52100 RC 55 BAR	
	05501	TFE/15% GLASS	
MS27980-XXN	10321	BRASS, ALL FORM	FASTENER,SNAP
	10360	BRONZE PHOSPHOR SAE 660	
	10308	PLATING NICKEL ELECTRODEPOSIT	
MS27981-1N/3N	10321	BRASS,ALL FORM	FASTENER,SNAP
	10322	BRONZE PHOSPHOR ALL FORMS	
	20269	PAPER KRAFT	
	10308	PLATING NICKEL ELECTRODEPOSIT	
MS27981-4N/8N	10321	BRASS, ALL FORM	FASTENER,SNAP
	10308	PLATING NICKEL ELECTRODEPOSIT	
MS27983	10321	BRASS, ALL FORM	FASTENER,SNAP
	10308	PLATING NICKEL ELECTRODEPOSIT	
MS28773-XX	00016	TEFLON TFE	RETAINER
MS28774-XXX	00016	TEFLON TFE	RETAINER
MS28775	01784	RUBBER NITRILE	PACKING PREFORM
MS28775-246	00515	ANTI-SEIZE COATED	PACKING
	05668	BUNA-N	
MS28775-XXX	01784	RUBBER NITRILE MS28775	PACKING,PREFORM
MS28776MX-X	99011	SEE FILE FOR MATERIALS	SCRAPER,PISTON R
MS28778-XX	05204	RUBBER NITRILE (NRB)	PACKING,PREFORM
MS28782	00016	TEFLON TFE	RETAINER,PACKING
MS28783	00016	TEFLON TFE	RING,GASKET
MS28889-1	10321	BRASS, ALL FORM	VALVE,AIR
	30080	CRES 303 FREE MACHINING	
	30114	CRES 410 BAR PLATE	
	20224	LACQUER YELLOW	
	05499	RUBBER NITRILE	
	05345	RUBBER NITRILE	
	00016	TEFLON TFE	
MS29513-0XX	05002	RUBBER NITRILE	PACKING,PREFORM
MS29561	20231	RUBBER NITRILE	PACKING,PREFORM
MS3212	10431	CRES 300 SERIES NON-FREE MACH	SCREW,SELF-SEAL
	02976	RUBBER SILICONE	
MS3213	10431	CRES 300 SERIES NON-FREE MACH	SCREW,SELF-SEAL
	05095	RUBBER L449-65 FLUOROSIL GR-60	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS3339-XX-X	05353	NYLON PLASTIC	PLATE,MOUNTING
MS33537	30080	CRES 303 BAR FRG FREE MACHINE	INSERT
MS33540C	10391	CRES 302/304	LOCK WIRE
MS3367-X	05253	NYLON PLASTIC	STRAP,TIEDOWN
MS3420-3	20032	RUBBER NEOPRENE	ADAPTER,CABLE
MS3498-XX	30135	AL 2011 T3/T8 BAR ROD WIRE	GROMMET W/SCREW
	10276	COATING ANODIC TYPE 1	
	30080	CRES 303 FREE MACHINING	
	05983	CTNG GRAY 36231 ALKYD MELAMINE	
MS35191	30082	PLATING CADMIUM & CHROMATE	SCREW,MACHINE
	10470	STEEL CARBON CR ALLOY	
MS35206	30082	PLATING CADMIUM & CHROMATE	SCREW,MACHINE
	10358	STEEL SAE/AISI 1008-1010	
MS35207	30082	PLATING CADMIUM & CHROMATE	SCREW,MACHINE
	10358	STEEL SAE/AISI 1008-1010	
MS35218	10292	AL 2024-T6 BAR ROD & WIRE	SCREW,MACHINE
	10277	COATING ANODIC TYPE 2	
MS35233	10431	CRES 300 SERIES NON-FREE MACH	SCREW,MACHINE
MS35239	30082	PLATING CADMIUM & CHROMATE	SCREW,MACHINE
	10358	STEEL SAE/AISI 1008-1010	
MS35265	30082	PLATING CADMIUM & CHROMATE	SCREW,MACHINE
	10358	STEEL SAE/AISI 1008-1010	
MS35275	10268	CRES 300 SERIES FASTENER MATL	SCREW,MACHINE
MS35276	10268	CRES 300 SERIES FASTENER MATL	SCREW,MACHINE
	30080	CRES 303 FREE MACHINING	
MS35307	10268	CRES 300 SERIES FASTENER MATL	SCREW,CAP,HEX
MS35308	10268	CRES 300 SERIES FASTENER MATL	SCREW,CAP,HEX
MS35333	99011	SEE FILE FOR MATERIALS	WASHER,LOCK
MS35335	99011	SEE FILE FOR MATERIALS	WASHER,LOCK
MS35337	99011	SEE FILE FOR MATERIALS	WASHER,LOCK
MS35338	10268	CRES 300 SERIES	WASHER
MS35430	10333	CU SHT PLT BAR ANN	TERMINAL,LUG
	10312	PLATING TIN E DEP/HT SOLDER DP	

MSFC-HDBK-527 REV F 9999942 0007123 5

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS35431	10333	CU SHT PLT BAR ANN	TERMINAL,LUG
	10312	PLATING TIN E DEP/HT SOLDER DP	
MS35489-XX	05484	RUBBER SYNTHETIC	GROMMET
MS35649	99011	SEE FILE FOR MATERIALS	NUT,PLAIN
MS35649-2X4	10268	CRES 300 SERIES	NUT
MS35650-XX4	10268	CRES 300 SERIES FASTENER MATL	NUT,PLAIN
MS35672	10431	CRES 300 SERIES NON-FREE MACH	PIN,TAPER
	30080	CRES 303 FREE MACHINING	
MS35675	10268	CRES 300 SERIES FASTENER MATL	PIN,STRAIGHT
	30080	CRES 303 FREE MACHINING	
MS35691	99011	SEE FILE FOR MATERIALS	NUT,PLAIN
MS35756	10513	STEEL 4XXX/8XXX OVER 220 KSI	KEY,WOODRUFF
MS35821-XA	10171	AL 5052-0 SHEET & PLATE	HINGE,BUTT
	10112	AL 5052-H32/34 SHEET & PLATE	
MS35827-XC	10350	CRES 301/302 ANN SHT STDS ONLY	HINGE,PIANO
MS35829	10431	CRES 300 SERIES NON-FREE MACH	HINGE,BUTT
MS35842	30150	CRES 200 SERIES	CLAMP,HOSE
	10431	CRES 300 SERIES NON-FREE MACH	
	30149	CRES 400 SERIES	
MS39086-462	10294	CRES 302 ANN THRU 1/2 HD PT SH	PIN,SPRING
MS45901	10321	BRASS, ALL FORM	WASHER,FLAT,ELEC
	10281	PLATING SILVER,FASTENERS ONLY	
	10312	PLATING TIN E DEP/HT SOLDER DP	
MS45932	10267	CRES A286 FASTENER MATL ONLY	
MS51021	10268	CRES 300 SERIES FASTENER MATL	SETSCREW
	30080	CRES 303 FREE MACHINING	
	00019	NYLON PLASTIC	
MS51023	10268	CRES 300 SERIES FASTENER MATL	SETSCREW
	30080	CRES 303 FREE MACHINING	
	00019	NYLON PLASTIC	
MS51029-1XX	10268	CRES 300 SERIES FASTENER MATL	SETSCREW
	00019	NYLON PLASTIC	
MS51031-1XX	10431	CRES 300 SERIES NON-FREE MACH	SETSCREW
	00019	NYLON PLASTIC	
MS51047	10268	CRES 300 SERIES FASTENER MATL	SETSCREW

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS51377	10321	BRASS, ALL FORM	VALVE CORE
	10308	PLATING NICKEL ELECTRODEPOLIT	
MS51606	10268	CRES 300 SERIES FASTENER MATL	PIN,HEADLESS
MS51607	10360	BRONZE PHOSPHOR SAE 660	PIN,HEADLESS
	10431	CRES 300 SERIES NON-FREE MACH	
MS51830-XXX	30080	CRES 303 FREE MACHINING	INSERT,SCREW THD
MS51830CAXXL	10382	CRES 302 ANN BAR SHP FRG WIRE	INSERT,SCREW THD
	10011	CRES A286 140 KSI BAR FRG TBNG	
	00597	LUBE DRY	
MS51831-XXL	10282	CRES 302 ANN BAR SHP FRG WIRE	INSERT,SCREW THD
	30080	CRES 303 FREE MACHINING	
	00597	LUBE DRY	
MS51831CAXXX	10267	CRES A286 FASTENER MATL ONLY	INSERT,SCREW THD
MS51844	10431	CRES 300 SERIES NON-FREE MACH	SLEEVE,SWAGING
MS51922-18	30080	CRES 303 FREE MACHINING	NUT,SELF-LOCKING
	00019	NYLON PLASTIC	
MS51922-41	00019	NYLON PLASTIC	NUT,SELF-LOCKING
	30082	PLATING CADMIUM & CHROMATE	
	30130	STEEL LOW ALLOY 17-22A RC32-36	
MS51923-114	10391	CRES 302	SPRING PIN
MS51923-147	10391	CRES 302 WIRE COND. B SPRING	PIN
MS51923-150	10431	CRES 300 SERIES NON-FREE MACH	PIN,SPRING
MS51923-298	10315	CRES 302	PIN
MS51923-398	10391	CRES 302	SPRING PIN
MS51937	10470	STEEL CARBON OR ALLOY	BOLT,EYE & SHLDR
MS51942	10322	BRONZE PHOSPHOR ALL FORMS	RIVET
MS51957	10268	CRES 300 SERIES FASTENER MATL	SCREW,MACHINE
	30080	CRES 303 FREE MACHINING	
MS51958-X	10268	CRES 300 SERIES FASTENER MATL	SCREW,MACHINE
	30080	CRES 303 FREE MACHINING	
MS51959	10268	CRES 300 SERIES FASTENER MATL	SCREW,MACHINE
	30080	CRES 303 FREE MACHINING	
MS51960	10268	CRES 300 SERIES FASTENER MATL	SCREW,MACHINE
	30080	CRES 303 FREE MACHINING	

MSFC-HDBK-527 REV F 9999942 0007125 9

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS51963-XX	30082	PLATING CADMIUM & CHROMATE	SETSCREW
	10513	STEEL 4XXX/8XXX OVER 220 KSI	
MS51965	30082	PLATING CADMIUM & CHROMATE	SETSCREW
	10486	STEEL 4340,4140,4130,8740	
MS51977	30082	PLATING CADMIUM & CHROMATE	SETSCREW
	10108	STEEL 4130 125-180 KSI	
MS51992C	10125	CRES A286 140 KSI BAR & FRG	STUD,LOCKED
MS51997	30082	PLATING CADMIUM & CHROMATE	RING,LOCK
	10359	STEEL AISI/SAE 1010 TO 1040	
MS51997E	10267	CRES A286 FASTENER MATL ONLY	RING,LOCK
MS541340	10279	AL 1100	EYELET
MS77067	10322	BRONZE PHOSPHOR, ALL FORMS	TERMINAL,LUG
	10312	PLATING TIN E DEP/HT SOLDER DP	
MS77070	10360	BRONZE PHOSPHOR SAE 660	TERMINAL,LUG
	10312	PLATING TIN E DEP/HT SOLDER DP	
MS8000	10416	CRES 17-4PH H1150 BAR ROD FORG	HOSE ASSEMBLY
	10091	CRES 304 COND B BAR SHP FRG WI	
	00597	LUBE DRY	
	00016	TEFLON TFE	
MS8005XXXXXA	30123	CRES 17-4 H900 BAR CST	HOSE ASSEMBLY
	30091	CRES 17-7PH TH1050 BAR & FRG	
	10382	CRES 302 ANN BAR SHP FRG WIRE	
	10089	CRES 302 COND B BAR AND WIRE	
	10351	CRES 304 ANN BAR SHP FRG WIRE	
	10098	CRES 321 ANN BAR SHP FRG WIRE	
	10100	CRES 347 ANN BAR SHP FRG WIRE	
	10085	CRES AM 355 SCT 1000 BAR FORG	
	00016	TEFLON TFE	
MS9021-027	06094	RUBBER N506-65 NITRILE	PACKING,PREFORM
MS9025	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS90376	05631	POLYETHYLENE	DUST CAP
MS90453-XX-XX	10352	CU WIRE GOLD PLTD (ELEC CONN)	CONTACT,ELEC PIN
MS90484-XX-1	02976	RUBBER SILICONE	GASKET,ELEC CONN
MS9068-XXX	05344	RUBBER SILICONE	PACKING,PREFORM
MS90727-XXX	50124	PLATING CADMIUM	SCREW,CAP
	30130	STEEL LOW ALLOY 17-22A	
MS9099	30105	AL 2014-T6,2024T6/T351 BAR	NUT,HEX
	10276	COATING ANODIC TYPE 1	

MSFC-HDBK-527 REV F 9999942 0007126 0

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS9100	10351	CRES 304 ANN BAR SHP FRG WIRE	NUT,HEX
MS9101-XX	10097	CRES 321 ANN SHT PLT STRIP	BRACKET,90 DEG
MS9102-XX	10097	CRES 321 ANN SHT PLT STRIP	BRACKET,90 DEG
MS9103-XX	10097	CRES 321 ANN SHT PLT STRIP	BRACKET,90 DEG
MS9104-XX	10097	321 CRES	BRACKET
MS9105	10148	SPRING 302 COND B WIRE	PIN,STRAIGHT
MS9105-XX	10520	WIRE CRES 302	PIN
MS9193	10351	CRES 304 ANN BAR SHP FRG WIRE	NIPPLE,TUBE
MS9198	10102	CRES 347 ANN TUBING SEAMLESS	NUT,TUBE COUPLNG
MS9201	10100 10281	CRES 347 ANN BAR SHP FRG WIRE PLATING SILVER,FASTENERS ONLY	GASKET,O-RING
MS9203-XXX	10101 10226	321 CRES 321 CRES	GASKET METAL O RING
MS9226	10009	NI-CR-FE WIRE ANN (INCO 600)	WIRE,SAFETY
MS9245	10098	CRES 321 ANN BAR SHP FRG WIRE	PIN,COTTER
MS9274	10097	CRES 321 ANN SHT PLT STRIP	WASHER,RETAINING
MS9321	10097	CRES 321 ANN SHT PLT STRIP	WASHER,FLAT
MS9355	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	CLAMP,LOOP
MS9356-10	10267	CRES A286	NUT
MS9358	10267	CRES A286 FASTENER MATL ONLY	NUT,HEX
MS9359	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENER ONLY	NUT,HEX
MS9360	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENER ONLY	NUT,HEX
MS9362-XX	10267 10281	CRES A286 FASTENER MATL. SH. PLATING SILVER	NUT,PLAIN HEXAGON
MS9363	10267	CRES A286 FASTENER MATL ONLY	NUT,HEX
MS9364-12	10267 10281	CRES A286 FASTENER MATL SH PLATING SILVER	STEEL NUT
MS9378	10097	CRES 321 ANN SHT PLT STRIP	COLLAR,TUBE CONN
MS9380	10279 10276	AL 11XX-0/HXX PLT & SHT COATING ANODIC TYPE 1	PLUG,EXPANSION

MSFC-HDBK-527 REV F 9999942 0007127 2

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS9387	05005	RUBBER VITON FLUID RESISTANT	O-RING
MS9388	05005	RUBBER VITON FLUID RESISTANT	PACKING,PREFORM
MS9389	10267	CRES A286 FASTENER MATL ONLY	PIN,STRAIGHT
MS9390	10267	CRES A286 FASTENER MATL SH	PIN
MS9390-160	10267	CRES A286	PIN
MS9390-180	10267	CRES A286	PIN
MS9390-190	10267	CRES A286	PIN
MS9390-200	10267	CRES A286	PIN
MS9390-420	10267	CRES A286	PIN
MS9390-580	10267	CRES A286	PIN
MS9391	10097	CRES 321 ANN SHT PLT STRIP	CLAMP,LOOP
MS9393-06	05571	RUBBER SILICONE	CUSHION,CLAMP
MS9405	10102 10281	CRES 347 ANN TUBING SEAMLESS PLATING SILVER,FASTENER ONLY	PLUG,MACHINE THD
MS9461	30002	CRES 440A,440B,440C BAR	BALL BEARING
MS9463	10267	CRES A286 FASTENER MATL ONLY	PIN,STRAIGHT
MS9483	10102	CRES 347 ANN TUBING SEAMLESS	FERRULE,BRAZING
MS9489	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
MS9498	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
MS9499	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
MS9500	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
MS9501	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
MS9549	10097	CRES 321 ANN SHT PLT STRIP	WASHER,FLAT
MS9549-12	10097	CRES 321	WASHER
MS9552	10097	CRES 321 ANN SHT PLT STRIP	BRACKET,FLAT
MS9556	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
MS9557	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
MS9565	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE

MSFC-HDBK-527 REV F ■ 9999942 0007128 4 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
MS9574-XX	10267 10281	A286 CRES SILVER PLATE	BOLT
MS9575-53	10267 10281	CRES A286 SILVER PLATE	BOLT
MS9575-XX	10267 10281	A286 CRES SILVER PLATE	BOLT
MS9584	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
MS9592	10097	CRES 321 ANN SHT PLT STRIP	BRACKET,ANGLE
MS9593-XXX	10097	CRES 321	BRACKET ANGLE
MS9594-XXX	10097	321 CRES	BRACKET
MS9595-XXX	10097	321 CRES	BRACKET
MS9600	30114	CRES 410 BAR PLATE	BRACKET,ANGLE
MS9676-05	10267	CRES A286	BOLT
MS9677-06	10267	CRES A286	BOLT MACHINE
MS9677-07	10267	CRES A286	BOLT MACHINE
MS9677-12	10267	CRES A286	BOLT MACHINE
MS9715	10281 30125	PLATING SILVER,FASTENER ONLY WASPALOY	BOLT,MACHINE
MS9841	30080	CRES 303 FREE MACHINING	KEY,WOODRUFF
MS9842	30090	STEEL GREEK ASCOLOY BAR FRG TB	PIN,STRAIGHT
MS9879	10102	CRES 347 ANN TUBING SEAMLESS	SLEEVE,TUBE CONN
MS9880-09	10097	CRES 321	WASHER
MS9880-10	10097	CRES 321	WASHER
MS9895-12	30090	418 CRES GREEK ASCOLOY	BOLT
MS9895-16	30090	418 CRES GREEK ASCOLOY	BOLT
MS9902-XX	10100	CRES 347 ANN BAR SHP FRG WIRE	PLUG,MACHINE THD
MS9954	30105 10276	AL 2014-T6,2024-T6/T851 BAR COATING ANODIC TYPE 1	PLUG,MACHINE THD
MSB501	10321 10431 05416 05929	BRASS, ALL FORM CRES 300 SERIES NON-FREE MACH CTNG CONVERSION BL OXIDE POTTG CPD FM1132 PHENOLIC	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
N2520-1/4 BLK	05353	NYLON PLASTIC	
NA112-0001-0509	10011	CRES A286	SCREW CAP SOCKET
		DRY FILM LUBE	
	10039	SILVER PLATE	
NA112-0001-0638	10011	CRES A286	SCREW CAP SOCKET
	05167	DRY FILM LUBE	
	10039	SILVER PLATE	
NAS 1068	10281	AG PLATING	NUT PLATE
	10267	CRES A286	
NAS 1100 E	10011	CRES A286	PAN HEAD SCREW
NAS 1100 V	10069	TI 6AL 4V	PAN HEAD SCREW
NAS 1101 E	10011	CRES A286	SCREW
NAS 1101 V	10069	TI 6AL 4V	SCREW
NAS 1102 E	10011	CRES A286	SCREW
	30082	PLATING CADIUM & CHROMATE	
NAS 1102 V	30082	PLATING CADIUM & CHROMATE	SCREW
	10069	TI 6AL 4V	
NAS 1122 E	10011	CRES A286	SCREW
NAS 1122 V	10069	TI 6AL 4V	SCREW
NAS 1291	10267	CRES A286	NUT SELF LOCKING HEX
NAS 1398 D	30099	AL 2017	INSERT
NAS 1399 D	10335	AL 2117-T4	RIVET
NAS 1411A	10366	AL 1100	BAND
NAS 1587 (ST 116)	10124		WASHER
		CRES A286	
NAS 1716	00016	TFE	CLAMP
NAS 1738 B	10443	AL 5056	RIVET
	30082	CADMIUM PLATED	
	10276	CTNG ANODIC T1	
	00666	CTNG CONVERSION CHROMATE	
	10222	MONEL	
	30096	STEEL 8740	
NAS 1738 M CR 2539	10222	MONEL	RIVET
	10135	NI INCONEL 600	
NAS 1739 A	10224	AL 2117-H13	RIVET
	00666	CTNG CONVERSION CHROMATE	

MSFC-HDBK-527 REV F ■ 9999942 0007130 2 ■

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS 1739 A	10135	INCO 600	RIVET
	10222	MONEL	
NAS 1739 B	10443	AL 5056	RIVET
	30082	CADMIUM PLATE	
	10276	CTNG ANODIC T1	
	00666	CTNG CONVERSION CHROMATE	
	10222	MONEL	
	30096	STEEL 8740	
NAS 1739 E	10443	AL5056	RIVET
	30082	CADMIUM PLATED	
	10276	CTNG ANODIC T1	
	00666	CTNG CONVERSION CHROMATE	
	10135	INCO 600	
	10222	MONEL	
NAS 1739 M	10135	INCO 600	RIVET
	10222	MONEL	
NAS 43DDX	30108	AL 2024 T3 FASTENERS ONLY	SPACER
NAS 509-XC	10267	CRES A286 FASTENER MATL SH	NUT
NAS 5402	10267	CRES A286	SCREW
	00019	NYLON PLASTIC	
NAS 5522	10606	CRES 18-8	CLAMP , MINOX
NAS 620AX	10112	AL 5052-H32 SHEET & PLATE	WASHER
NAS1/23F3	10267	CRES A286 FASTENER MATL SH	SCREW
NAS1003	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1004	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1005	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1006	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1007	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1008	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1009	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1010	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1011	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1012	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1013	10267.	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1014	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1015	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1016	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1017	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1018	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1019	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1020	10267	CRES A286 FASTENER MATL ONLY	BOLT,MACHINE
NAS1021CX	10268 10281	CRES 300 SERIES FASTENER MATL PLATING SILVER,FASTENERS ONLY	NUT,SELF-LOCKING
NAS1022CX	10268 10281	CRES 300 SERIES FASTENER MATL PLATING SILVER,FASTENERS ONLY	NUT,SELF-LOCKING
NAS1031C	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENERS ONLY	NUT,SELF-LOCKING
NAS1033	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENERS ONLY	NUT,SELF-LOCKING
NAS1051T	30080	CRES 303 FREE MACHINING	SPACER,SLEEVE
NAS1056C	10506	CRES 303/304 BAR AND WIRE	SPACER,SLEEVE
NAS1056E	10267	CRES A286 FASTENER MATL ONLY	SPACER,SLEEVE
NAS1057W	10267	CRES A286 FASTENER MATL ONLY	SPACER,SLEEVE
NAS1060	10501 10328 10281	CU RODS & SHAPES PLATING GOLD PLATING SILVER,FASTENERS ONLY	TERMINAL BLOCK
NAS1062	01883	LAMIN GLASS/SILICONE	STRIP,NUT INSUL
NAS1063	00895 01883	ADHES DC 281 SILICONE LAMIN GLASS/SILICONE	STRIP,BASE INSUL
NAS1065	30080	CRES 303 BAR FRG FREE MACHINE	STUD
NAS1067CX	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENERS ONLY	NUT PLATE
NAS1068C	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENERS ONLY	NUT PLATE
NAS1068CXXXM	10267	CRES A286 FASTENER MATL ONLY	NUT PLATE
NAS1080-XX	30111 05168 10277	AL 2024-T3/T4 SHEET CETYL ALCOHOL 96 PERCENT COATING ANODIC TYPE 2	COLLAR,SWAGE LOK

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1080DXX	50119	AL6061-H13 HEAT TREAT TO-T7	COLLAR,SWAGE LOK
	60059	CETYL ALCOHOL	
NAS1081	30080	CRES 303 FREE MACHINING	SETSCREW,LOCKING
NAS1090	10148	SPRING 302 COND B WIRE	HOOK,CHAIN
	10419	SPRING TEMPER CRES 302 WIRE	
NAS1097AD	10335	AL 2117-T4 ANN WIRE (RIVETS)	RIVET,SOLID
	10276	COATING ANODIC TYPE 1	
	00666	CTNG CONVERSION CHROMATE INORG	
NAS1097DD	30112	AL2024-T3/T4 PLATE BAR TUBE	RIVET,SOLID
	10277	COATING ANODIC TYPE 2	
NAS1099-XX	50124	PLATING CADMIUM	WASHER,BEVEL
	30130	STEEL LOW ALLOY 17-22A	
NAS1100-XX	30082	PLATING CADMIUM & CHROMATE	SCREW,MACHINE
	10123	STEEL 4140 180KSI BAR & FORG	
NAS1100CXX	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1100EXX	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1101CXX	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1101EXX	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1102CXX	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1102E04-7	10267	CRES A286 FASTENER MATL SH	SCREWS
	10281	PLATING SILVER	
NAS1102EXX	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1121C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1121E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1122C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1122E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1123C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1123E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1124C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1124E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1125C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1125E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE

MSFC-HDBK-527 REV F 9999942 0007133 8

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1126C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1126E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1127C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1127E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1128C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1128E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1131C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1131E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1132C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1132E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1133C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1133E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1134C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1134E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1135C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1135E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1136C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1136E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1137C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1137E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1138C	10011	CRES A286 140 KSI BAR FRG TBNG	SCREW,MACHINE
NAS1138E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1151	30082 50145	PLATING CADMIUM & CHROMATE STEEL 4XXX/8XXX BELOW 180KSI	SCREW,MACHINE
NAS1151E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1151V	10365	TI 6AL-4V-STA BAR & FORGINGS	SCREW,MACHINE
NAS1152	30082 50145	PLATING CADMIUM & CHROMATE STEEL 4XXX/8XXX BELOW 180KSI	SCREW,MACHINE
NAS1152E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1152V	10365	TI 6AL-4V-STA BAR & FORGINGS	SCREW,MACHINE
NAS1153	30082 50145	PLATING CADMIUM & CHROMATE STEEL 4XXX/8XXX BELOW 180KSI	SCREW,MACHINE
NAS1153E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1153V	10365	TI 6AL-4V-STA BAR & FORGINGS	SCREW,MACHINE
NAS1154	30082 50145	PLATING CADMIUM & CHROMATE STEEL 4XXX/8XXX BELOW 180KSI	SCREW,MACHINE
NAS1154E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1154V	10365	TI 6AL-4V-STA BAR & FORGINGS	SCREW,MACHINE
NAS1155	30082 50145	PLATING CADMIUM & CHROMATE STEEL 4XXX/8XXX BELOW 180KSI	SCREW,MACHINE
NAS1155E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1155V	10365	TI 6AL-4V-STA BAR & FORGINGS	SCREW,MACHINE
NAS1156	30082 50145	PLATING CADMIUM & CHROMATE STEEL 4XXX/8XXX BELOW 180KSI	SCREW,MACHINE
NAS1156E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1156V	10365	TI 6AL-4V-STA BAR & FORGINGS	SCREW,MACHINE
NAS1157	30082 50145	PLATING CADMIUM & CHROMATE STEEL 4XXX/8XXX BELOW 180KSI	SCREW,MACHINE
NAS1157E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1157V	10365	TI 6AL-4V-STA BAR & FORGINGS	SCREW,MACHINE
NAS1158	30082 50145	PLATING CADMIUM & CHROMATE STEEL 4XXX/8XXX BELOW 180KSI	SCREW,MACHINE
NAS1158E	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS1158V	10365	TI 6AL-4V-STA BAR & FORGINGS	SCREW,MACHINE
NAS1169C	10267	CRES A286 FASTENER MATL ONLY	WASHER,DIMPLED
NAS1169DD	10408 10277	AL 2024T3/T4X/T6X/T8XX CLD SHT COATING ANODIC TYPE 2	WASHER,DIMPLED
NAS1171EXXN	10267 61114	CRES A286 FASTENER MATL SH PLASTIC NYLON 12	SCREW
NAS1181-88C/EXK	10267 05084	CRES A286 FASTENER MATL ONLY KEL-F UNPLASTICIZED	SCREW,SELF LOCKG

MSFC-HDBK-527 REV F ■ 9999942 0007135 1 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1189CXXTXL	10011 00019	CRES A286 140 KSI BAR FRG TBNG NYLON PLASTIC	SCREW,SELF LOCKG
NAS1189EXXTXL	10267 00019	CRES A286 FASTENER MATL ONLY NYLON PLASTIC	SCREW,SELF LOCKG
NAS1189EXXTXLK	10267 05084	CRES A286 FASTENER MATL ONLY KEL-F UNPLASTICIZED	SCREW,SELF LOCKG
NAS1190CXXPXXL	50077 00019	CRES A286 (130-140 KSI) NYLON PLASTIC	SCREW,SELF LOCKG
NAS1190EXXTXXLK	10267 05084	CRES A286 FASTENER MATL ONLY KEL-F UNPLASTICIZED	SCREW,SELF-LOCKG
NAS1190EXXTXXN	10267 00019	CRES A286 FASTENER MATL ONLY NYLON PLASTIC	SCREW,SELF-LOCKG
NAS1190XEXL	10267 61114	CRES A286 FASTENER MATL SH PLASTIC NYLON 12	SCREW
NAS1191EXXXXXN	10267 00019	CRES A286 FASTENER MATL ONLY NYLON PLASTIC	SCREW,SELF-LOCKG
NAS1191EXXXXXNK	10267 05084	CRES A286 FASTENER MATL ONLY KEL-F UNPLASTICIZED	SCREW,SELF-LOCKG
NAS1193KX	10378	CRES 17-4PH H1025 CASTING	LOCKING DEVICE
NAS1195DXXX	10503 10277	AL 5052-H32/H34/H36 SHT PLT COATING ANODIC TYPE 2	SHIM
NAS1197-X	10112	AL 5052-H32 SHEET & PLATE	WASHER
NAS1198	10267	CRES A286 FASTENER MATL ONLY	RIVET,SOLID
NAS1199	10267	CRES A286 FASTENER MATL ONLY	RIVET,SOLID
NAS1200	10267	CRES A286 FASTENER MATL ONLY	RIVET,SOLID
NAS1201C	10431	CRES 300 SERIES NON-FREE MACH	CHAIN-BEAD
NAS1216-XXE	10267	CRES A286 FASTENER MATL ONLY	SCREW,PAN HEAD
NAS1218-XE-XX	50140	CRES A286 160 KSI BAR FRG TBG	BOLT,PAN HEAD
NAS1218-XV-XX	10067	TI 6AL 4V ANN EXTR BAR ROD	BOLT,PAN HEAD
NAS1219-XC-XX	10267	CRES A286 FASTENER MATL ONLY	SCREW,FLUSH HEAD
NAS1219-XCR-XX	10089 10336	CRES 302 COND B BAR AND WIRE CRES 305 ANN BAR	SCREW,FLUSH HEAD
NAS1219-XE-XX	50140	CRES A286 160 KSI BAR FRG TBG	SCREW,FLUSH HEAD

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1221-XE-XX	50140	CRES A286 160 KSI BAR FRG TBG	BOLT,CSK HEAD
NAS1223	00019	NYLON PLASTIC	BOLT,SHEAR
	50124	PLATING CADMIUM	
	50127	STEEL 4340 160-180 KSI BAR FRG	
NAS1223C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
	00019	NYLON PLASTIC	
NAS1224	00019	NYLON PLASTIC	BOLT,SHEAR
	50124	PLATING CADMIUM	
	50127	STEEL 4340 160-180 KSI BAR FRG	
NAS1224C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
	00019	NYLON PLASTIC	
NAS1225	00019	NYLON PLASTIC	BOLT,SHEAR
	50124	PLATING CADMIUM	
	50127	STEEL 4340 160-180 KSI BAR FRG	
NAS1225C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
	00019	NYLON PLASTIC	
NAS1226	00019	NYLON PLASTIC	BOLT,SHEAR
	50124	PLATING CADMIUM	
	50127	STEEL 4340 160-180 KSI BAR FRG	
NAS1226C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
	00019	NYLON PLASTIC	
NAS1227	00019	NYLON PLASTIC	BOLT,SHEAR
	50124	PLATING CADMIUM	
	50127	STEEL 4340 160-180 KSI BAR FRG	
NAS1227C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
	00019	NYLON PLASTIC	
NAS1228	00019	NYLON PLASTIC	BOLT,SHEAR
	50124	PLATING CADMIUM	
	50127	STEEL 4340 160-180 KSI BAR FRG	
NAS1228C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
	00019	NYLON PLASTIC	
NAS1229	00019	NYLON PLASTIC	BOLT,SHEAR
	50124	PLATING CADMIUM	
	50127	STEEL 4340 160-180 KSI BAR FRG	
NAS1229C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
	00019	NYLON PLASTIC	
NAS1230	00019	NYLON PLASTIC	BOLT,SHEAR
	50124	PLATING CADMIUM	
	50127	STEEL 4340 160-180 KSI BAR FRG	

MSFC-HDBK-527 REV F ■ 9999942 0007137 5 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1230C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
	00019	NYLON PLASTIC	
NAS1231	00019	NYLON PLASTIC	BOLT,SHEAR
	50124	PLATING CADMIUM	
	50127	STEEL 4340 160-180 KSI BAR FRG	
NAS1231C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
	00019	NYLON PLASTIC	
NAS1232	00019	NYLON PLASTIC	BOLT,SHEAR
	50124	PLATING CADMIUM	
	50127	STEEL 4340 160-180 KSI BAR FRG	
NAS1232C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
	00019	NYLON PLASTIC	
NAS1233	00019	NYLON PLASTIC	BOLT,SHEAR
	50124	PLATING CADMIUM	
	50127	STEEL 4340 160-180 KSI BAR FRG	
NAS1233C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
	00019	NYLON PLASTIC	
NAS1234	00019	NYLON PLASTIC	BOLT,SHEAR
	50124	PLATING CADMIUM	
	50127	STEEL 4340 160-180 KSI BAR FRG	
NAS1234C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
	00019	NYLON PLASTIC	
NAS1235	00019	NYLON PLASTIC	BOLT,SHEAR
	50124	PLATING CADMIUM	
	50127	STEEL 4340 160-180 KSI BAR FRG	
NAS1235C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
	00019	NYLON PLASTIC	
NAS1252	10028	AL 7075-T6 SHEET	WASHER,FLAT
	10277	COATING ANODIC TYPE 2	
NAS1291CXX	10267	CRES A286 FASTENER MATL ONLY	NUT,SELF-LOCKING
	10281	PLATING SILVER,FASTENER ONLY	
NAS1291CXXM	10267	CRES A286 FASTENER MATL ONLY	NUT,SELF-LOCKING
	05723	LUBE DRY	
NAS1292R	10373	RENE 41 170 KSI	PIN-THREADED
NAS1293R	10373	RENE 41 170 KSI	PIN-THREADED
NAS1294R	10373	RENE 41 170 KSI	PIN-THREADED
NAS1295R	10373	RENE 41 170 KSI	PIN-THREADED

MSFC-HDBK-527 REV F 9999942 0007138 7

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1296R	10373	RENE 41 170 KSI	PIN-THREADED
NAS1303	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1304	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1305	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1306	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1307	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1308	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1309	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1310	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1311	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1312	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1313	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1314	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1315	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1316	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1317	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1318	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1319	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR
NAS1320	50124 50127	PLATING CADMIUM STEEL 4340 160-180 KSI BAR FRG	BOLT,SHEAR

MSFC-HDBK-527 REV F ■ 9999942 0007139 9 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1329AXXXXX	50120	AL 6053-T4 RIVET MATERIAL	NUT,BLIND RIVET
	10277	COATING ANODIC TYPE 2	
NAS1329CXXXXX	50120	CRES 430 WIRE PASSIVATED	NUT,BLIND RIVET
NAS1333	10399	CRES 17-4PH H1025 BAR FRG RING	PIN,QUICK RELEAS
	30124	CRES 17-4PH H900/15-7MO TH1050	
	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	10264	SPRING TEMPER 15-7MO RH950	
NAS1334	10399	CRES 17-4PH H1025 BAR FRG RING	PIN,QUICK RELEAS
	30124	CRES 17-4PH H900/15-7MO TH1050	
	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	10264	SPRING TEMPER 15-7MO RH950	
NAS1335	10399	CRES 17-4PH H1025 BAR FRG RING	PIN,QUICK RELEAS
	30124	CRES 17-4PH H900/15-7MO TH1050	
	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	10264	SPRING TEMPER 15-7MO RH950	
NAS1336	10399	CRES 17-4PH H1025 BAR FRG RING	PIN,QUICK RELEAS
	30124	CRES 17-4PH H900/15-7MO TH1050	
	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	10264	SPRING TEMPER 15-7MO RH950	
NAS1337	10399	CRES 17-4PH H1025 BAR FRG RING	PIN,QUICK RELEAS
	30124	CRES 17-4PH H900/15-7MO TH1050	
	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	10264	SPRING TEMPER 15-7MO RH950	
NAS1338	10399	CRES 17-4PH H1025 BAR FRG RING	PIN,QUICK RELEAS
	30124	CRES 17-4PH H900/15-7MO TH1050	
	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	10264	SPRING TEMPER 15-7MO RH950	
NAS1339	10399	CRES 17-4PH H1025 BAR FRG RING	PIN,QUICK RELEAS
	30124	CRES 17-4PH H900/15-7MO TH1050	
	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	10264	SPRING TEMPER 15-7MO RH950	
NAS1340	10399	CRES 17-4PH H1025 BAR FRG RING	PIN,QUICK RELEAS
	30124	CRES 17-4PH H900/15-7MO TH1050	
	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	10264	SPRING TEMPER 15-7MO RH950	
NAS1341	10399	CRES 17-4PH H1025 BAR FRG RING	PIN,QUICK RELEAS
	30124	CRES 17-4PH H900/15-7MO TH1050	
	30080	CRES 303 FREE MACHINING	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1341	30002	CRES 440A,440B,440C BAR	PIN,QUICK RELEAS
	10264	SPRING TEMPER 15-7MO RH950	
NAS1342	10399	CRES 17-4PH H1025 BAR FRG RING	PIN,QUICK RELEAS
	30124	CRES 17-4PH H900/15-7MO TH1050	
	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	10264	SPRING TEMPER 15-7MO RH950	
NAS1343	10399	CRES 17-4PH H1025 BAR FRG RING	PIN,QUICK RELEAS
	30124	CRES 17-4PH H900/15-7MO TH1050	
	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	10264	SPRING TEMPER 15-7MO RH950	
NAS1344	10399	CRES 17-4PH H1025 BAR FRG RING	PIN,QUICK RELEAS
	30124	CRES 17-4PH H900/15-7MO TH1050	
	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	10264	SPRING TEMPER 15-7MO RH950	
NAS1345	10399	CRES 17-4PH H1025 BAR FRG RING	PIN,QUICK RELEAS
	30124	CRES 17-4PH H900/15-7MO TH1050	
	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	10264	SPRING TEMPER 15-7MO RH950	
NAS1346	10399	CRES 17-4PH H1025 BAR FRG RING	PIN,QUICK RELEAS
	30124	CRES 17-4PH H900/15-7MO TH1050	
	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	10264	SPRING TEMPER 15-7MO RH950	
NAS1351-XXXXX	20132	CTNG BLACK OXIDE (INORGANIC)	SCREW,CAP
	30130	STEEL LOW ALLOY 1M-22A RC32-36	
NAS1351-XXXXXP	50124	PLATING CADMIUM	SCREW,CAP
	30130	STEEL LOW ALLOY 1M-22A RC32-36	
NAS1351CX	10268	CRES 300 SERIES FASTENER MATL	SCREW,CAP
NAS1351CXLXX	10268	CRES 300 SERIES FASTENER MATL	SCREW,CAP
	00019	NYLON PLASTIC	
NAS1351NX	50140	CRES A286 160 KSI BAR FRG TBG	SCREW,CAP
NAS1352C	10268	CRES 300 SERIES FASTENER MATL	SCREW,CAP
NAS1352N	50140	CRES A286 160 KSI BAR FRG TBG	SCREW,CAP
NAS1368	00019	NYLON PLASTIC	GROMMET
NAS1373A16SF014	10360	BRONZE PHOSPHOR SAE 660	DUCT,AIR
	05120	FABRIC 7021G 1528 GLASS/SIL	
	00777	FABRIC FIBERGLAS (INORGANIC)	
	10232	SPRING STEEL MUSIC WIRE	

MSFC-HDBK-527 REV F ■ 9999942 0007141 7 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1387	50114	CU TERMINAL	LUG,CRIMP STYLE
	10312	PLATING TIN	
	20017	TUBING POLYOLEFIN HST	
NAS1393CX	10267	CRES A286 FASTENER MATL SH	SCREW
	10281	PLATING SILVER	
NAS1394CA3S	10267	CRES A286	INSERT
	10281	SILVER PLATE	
NAS1394CA4	10267	CRES A286	INSERT
	10281	SILVER PLATE	
NAS1394CA4S	10267	CRES A286	INSERT
	10281	SILVER PLATE	
NAS1394CAXXXLSN	10267	CRES A286 FASTENER MATL ONLY	INSERT,SELF-LOK
	10281	PLATING SILVER, FASTENERS ONLY	
NAS1394CX	30080	CRES 303 BAR FRG FREE MACHINE	INSERT
	10281	PLATING SILVER	
NAS1394CXXL	30080	CRES 303	INSERT
NAS1395CA5S	10267	CRES A286	INSERT
	10281	SILVER PLATE	
NAS1395CA6L	10267	CRES A286	INSERT
	05167	DRY FILM COAT	
NAS1395CAXX	10267	CRES A286 FASTENER MATL ONLY	INSERT,SELF-LOK
	10281	PLATING SILVER,FASTENERS ONLY	
NAS1395CX	30080	CRES 303 BAR FRG FREE MACHINE	INSERT
	10267	CRES A286 FASTENER MATL SH	
	10281	PLATING SILVER	
NAS1395CXX	30080	CRES 303 FREE MACHINING	INSERT,SELF-LOK
NAS1398B	10443	AL 5056	RIVET , BLIND
	50238	AL 5056-H38	
	10603	AL 7075	
	10276	CTNG ANODIC TYPE 1	
	00666	CTNG CONVERSION CHROMATE INORG	
NAS1398BX-XX	10443	AL 5056-0/H32 ROD & WIRE	RIVET,BLIND
	10261	AL 5056-H191 FOIL	
	10603	AL 7075-0 ROD WIRE	
	10276	COATING ANODIC TYPE 1	
	00666	CTNG CONVERSION CHROMATE INORG	
NAS1398CSX-XX	10267	CRES A286 FASTENER MATL ONLY	RIVET,BLIND
	10222	MONEL 400/405 ALL FORMS	
	10039	PLATING SILVER	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1398CX-X	10267	CRES A286 FASTENER MATL SH	RIVET
	10222	MONEL 400 67NI 30CU ANN WIRE	
NAS1398CX-XX	10267	CRES A286 FASTENER MATL ONLY	RIVET,BLIND
	10222	MONEL 400/405 ALL FORMS	
NAS1398DX-XX	99010	NOT TO BE USED ON SHUTTLE	RIVET,BLIND
NAS1399BX-XX	10261	AL 5056-H191 FOIL	RIVET,BLIND
	10443	AL5056-0/H32 ROD & WIRE	
	30122	AL7075-T6XX BAR EXTR PLATE	
	10276	COATING ANODIC TYPE 1	
	00666	CTNG CONVERSION CHROMATE INORG	
NAS1399CX-XX	10268	CRES 300 SERIES FASTENER MATL	RIVET,BLIND
	10222	MONEL 400/405 ALL FORMS	
NAS1401-XCX	10268	CRES 300 SERIES FASTENER MATL	WASHER,RADIUS
NAS1401-XDX	30111	AL 2024-T3/T4 SHEET	WASHER,RADIUS
	10276	COATING ANODIC TYPE 1	
	00666	CTNG CONVERSION CHROMATE INORG	
NAS1407NXXX	10382	CRES 302 ANN BAR SHP FRG WIRE	PIN,SPRING
NAS1411C010A020	10294	CRES 302	BAND
NAS1411C012A030	10294	CRES 302	BAND
NAS1423C	10267	CRES A286 FASTENER MATL ONLY	NUT,HEX
NAS1435	10350	CRES 301/302 ANN SHT STDS ONLY	TERMINAL STRIP
NAS1454C	30080	CRES 303 FREE MACHINING	ROD,THREADED
	50124	PLATING CADMIUM	
NAS1464BXXX-XXN	10308	PLATING NICKEL ELECTRODEPOSIT	CLIP,SPRING TENS
	10149	SPRING BE-CU AT WIRE & STRIP	
NAS1474CXX	10267	CRES A286 FASTENER MATL ONLY	NUT,SELF-LOCKING
	10281	PLATING SILVER,FASTENERS ONLY	
	05344	RUBBER SILICONE	
NAS1515MXX	00016	TEFLON TFE	WASHER,RUBBER
NAS1523-XL	30082	PLATING CADMIUM & CHROMATE	PACKING W/RETAIN
	10108	STEEL 4130 125-180 KSI SHT PLT	
	00016	TEFLON TFE	
NAS1523CXE	10350	CRES 301/302 ANN SHT STDS ONLY	PACKING W/RETAIN
	05005	RUBBER VITON FLUID RESISTANT	
NAS1523CXXN	10350	CRES 301/302 ANN SHT STDS ONLY	PACKING W/RETAIN
	05725	RUBBER B318-70 BUTYL	

MSFC-HDBK-527 REV F 9999942 0007143 0

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1564JXX	10351	CRES 304 ANN BAR SHP FRG WIRE	REDUCER,TUBE
NAS1578CXXX	10267	CRES A286 FASTENER MATL ONLY	BOLT,PAN HEAD
NAS1578CXXXP	10267 50124	CRES A286 FASTENER MATL ONLY PLATING CADMIUM	BOLT,PAN HEAD
NAS1578VXXX	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,PAN HEAD
NAS1579C	10267	CRES A286 FASTENER MATL ONLY	BOLT,PAN HEAD
NAS1580C	10267	CRES A286 FASTENER MATL ONLY	BOLT,FLUSH HEAD
NAS1581C	10267	CRES A286 FASTENER MATL ONLY	BOLT,FLUSH HEAD
NAS1581V	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,FLUSH HEAD
NAS1587	10289	CRES 321/347 ANN SHT STDS	WASHER,PLAIN
NAS1593-XXX	05005	RUBBER VITON FLUID RESISTANT	PACKING,PREFORM
NAS1595	05005	RUBBER VITON FLUID RESISTANT	PACKING,PREFORM
NAS1596	05005	RUBBER VITON FLUID RESISTANT	PACKING,PREFORM
NAS1598CXXN	10088 05922	CRES 301 ANN THRU 1/2 HD PT SH RUBBER BUTYL 70 SHORE	WASHER,SEALING
NAS1598CXXR	10088 05095	CRES 301 ANN THRU 1/2 HD PT SH RUBBER L449-65 FLUOROSIL GR-60	WASHER,SEALING
NAS1598CXXY	10088 20231	CRES 301 ANN THRU 1/2 HD PT SH RUBBER NITRILE MS29561-005	WASHER,SEALING
NAS1598DXXR	10028 10277 05095	AL 7075-T6 SHEET COATING ANODIC TYPE 2 RUBBER L449-65 FLUOROSIL GR-60	WASHER,SEALING
NAS1611	01455	RUBBER E515-8 EPR	PACKING,PREFORM
NAS1612	01455	RUBBER E515-8 EPR	PACKING, PREFORM
NAS1613	01455	RUBBER E515-8 EPR	PACKING, PREFORM
NAS1620E	10267	CRES A286 FASTENER MATL ONLY	SCREW, MACHINE
NAS1621E	10267	CRES A286 FASTENER MATL ONLY	SCREW, MACHINE
NAS1622E	10267	CRES A286 FASTENER MATL ONLY	SCREW, MACHINE
NAS1623E	10267	CRES A286 FASTENER MATL ONLY	SCREW, MACHINE
NAS1624E	10267	CRES A286 FASTENER MATL ONLY	SCREW, MACHINE
NAS1625E	10267	CRES A286 FASTENER MATL ONLY	SCREW, MACHINE

MSFC-HDBK-527 REV F 9999942 0007144 2

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1626E	10267	CRES A286 FASTENER MATL ONLY	SCREW, MACHINE
NAS1627E	10267	CRES A286 FASTENER MATL ONLY	SCREW, MACHINE
NAS1628E	10267	CRES A286 FASTENER MATL ONLY	SCREW, MACHINE
NAS1630E	10267	CRES A286 FASTENER MATL ONLY	SCREW, MACHINE
NAS1631E	10267	CRES A286 FASTENER MATL ONLY	SCREW, MACHINE
NAS1632E	10267	CRES A286 FASTENER MATL ONLY	SCREW, MACHINE
NAS1633E	10267	CRES A286 FASTENER MATL ONLY	SCREW, MACHINE
NAS1634E	10267	CRES A286 FASTENER MATL ONLY	SCREW, MACHINE
NAS1635-XX	10268	CRES 300 SERIES FASTENER MATL	SCREW, MACHINE
	30080	CRES 303 FREE MACHINING	
NAS1635-XXLX	10268	CRES 300 SERIES FASTENER MATL	SCREW,MACHINE
	30080	CRES 303 FREE MACHINING	
	00019	NYLON PLASTIC	
NAS1640	10268	CRES 300 SERIES FASTENER MATL	WASHER,LOCK
NAS1671	99010	NOT TO BE USED ON SHUTTLE	FASTENER-BLIND
NAS1672-XXL	10267	CRES A286 FASTENER MATL ONLY	FASTENER-BLIND
NAS1676C	10268	CRES 300 SERIES FASTENER MATL	WASHER,LOCK-SPG
	30080	CRES 303 FREE MACHING	
NAS1715CTXT	10294	CRES 302 ANN THRU 1/2 HD PT SH	CLAMP,LOOP-CUSHD
	10097	CRES 321 ANN SHT PLT STRIP	
	00016	TEFLON TFE	
NAS1716CXXK	10268	CRES 300 SERIES FASTENER MATL	CLAMP ASSEMBLY
	00016	TEFLON TFE	
NAS1716CXXT	10268	CRES 300 SERIES FASTENER MATL	CLAMP ASSEMBLY
	00016	TEFLON TFE	
NAS1738E	10443	AL 5056-0/H32 ROD & WIRE	RIVET,BLIND
	10276	COATING ANODIC TYPE 1	
	00666	CTNG CONVERSION CHROMATE INORG	
	10222	MONEL 400/405 ALL FORMS	
	10009	NI-CR-FE WIRE ANN (INCO 600)	
NAS1745	00367	KYNAR HST PVF 2	SPLICE,CONDUCTOR
	10079	SOLDER SN 50/60/62/63	
	20064	THERMOPLASTIC THERMAL STABILIZ	
NAS1746	00367	KYNAR HST PVF 2	SPLICE,CONDUCTOR
	10079	SOLDER SN 50/60/62/63	
	20064	THERMOPLASTIC THERMAL STABILIX	

MSFC-HDBK-527 REV F 9999942 0007145 4

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1752	10267	CRES A286 FASTENER MATL ONLY	FASTENER,BLIND
NAS1753	10267	CRES A286 FASTENER MATL ONLY	FASTENER,BLIND
NAS1789CXXM	10267	CRES A286 FASTENER MATL ONLY	NUT,SELF-LOCKING
	06172	LUBE DRY MOLYKOTE Z MOS2 INORG	
NAS1919M	10399	CRES 17-4PH H1025 BAR FRG RIND	RIVET,BLIND
	10267	CRES A286 FASTENER MATL ONLY	
	10222	MONEL 400/405 ALL FORMS	
	30082	PLATING CADMIUM & CHROMATE	
NAS1922	10431	CRES 300 SERIES NON-FREE MACH	CLAMP,HOSE
	10088	CRES 301 ANN THRU 1/2 HD PT SH	
	30080	CRES 303 FREE MACHINING	
NAS1953C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1954C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1955C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1956C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1957C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1958C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1959C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1960C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1961C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1962C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1963C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1964C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1965C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1966C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1967C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1968C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1969C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1970C	10267	CRES A286 FASTENER MATL ONLY	BOLT,SHEAR
NAS1972C	50084	CRES A286 180 KSI BAR FRG	BOLT,TORQ-SET
NAS1973C	50084	CRES A286 180 KSI BAR FRG	BOLT,TORQ-SET

MSFC-HDBK-527 REV F 9999942 0007146 6

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS1974C	50084	CRES A286 180 KSI BAR FRG	BOLT,TORQ-SET
NAS1975C	50084	CRES A286 180 KSI BAR FRG	BOLT,TORQ-SET
NAS1976C	50084	CRES A286 180 KSI BAR FRG	BOLT,TORQ-SET
NAS1977C	50084	CRES A286 180 KSI BAR FRG	BOLT,TORQ-SET
NAS1978C	50084	CRES A286 180 KSI BAR FRG	BOLT,TORQ-SET
NAS1979C	50084	CRES A286 180 KSI BAR FRG	BOLT,TORQ-SET
NAS1980C	50084	CRES A286 180 KSI BAR FRG	BOLT,TORQ-SET
NAS42DD	30108 10276	AL 2024-T3/T4 FASTENER ONLY COATING ANODIC TYPE 1	SPACER-RIVET
NAS42DD4-8	30108	AL 2024 T3 FASTENERS ONLY	SPACER
NAS43	30108 10276	AL 2024-T3/T4 FASTENER ONLY COATING ANODIC TYPE 1	SPACER,SCREW
NAS43DD4-XX	30112 10276	2024-T3 AL ANODIZED	SPACER
NAS463-CXX	10268	CRES 300 SERIES FASTENER MATL	NUT SPACER
NAS463-DDXX	10457 10277	AL 7075-T6 CLAD SHEET COATING ANODIC TYPE 2	NUT SPACER
NAS463-DXX	10503 10277	AL 5052-H32/H34/H36 SHT PLT COATING ANODIC TYPE 2	NUT SPACER
NAS501	10390	CRES 321/347 ANN BR PLT TB	BOLT,CRS
NAS501-3H 4A	10100	CRES 321	BOLT
NAS509-XC	10267	CRES A286 FASTENER MATL ONLY	NUT,DRILLED JAM
NAS513	30082 10299	PLATING CADMIUM & CHROMATE SPRING STEEL 1095 COND 2	WASHER,ROD END
NAS513-X	50124	PLATING CADMIUM	WASHER
NAS514	30082 30096	PLATING CADMIUM & CHROMATE STEEL 8740 BAR FORGING RINGS	SCREW,MACHINE
NAS5400-	10267 30082	CRES A286 FASTENER MATL ONLY PLATING CADMIUM & CHROMATE	SCREW,MACHINE
NAS5400U	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS5401-	10267 30082	CRES A286 FASTENER MATL ONLY PLATING CADMIUM & CHROMATE	SCREW,MACHINE

MSFC-HDBK-527 REV F 9999942 0007147 8

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS5401U	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS5402-	10267 30082	CRES A286 FASTENER MATL ONLY PLATING CADMIUM & CHROMATE	SCREW,MACHINE
NAS5402U	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS5403-	10267 30082	CRES A286 FASTENER MATL ONLY PLATING CADMIUM & CHROMATE	SCREW,MACHINE
NAS5403U	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS5404-	10267 30082	CRES A286 FASTENER MATL ONLY PLATING CADMIUM & CHROMATE	SCREW,MACHINE
NAS5404U	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS5405-	10267 30082	CRES A286 FASTENER MATL ONLY PLATING CADMIUM & CHROMATE	SCREW,MACHINE
NAS5405U	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS5406-	10267 30082	CRES A286 FASTENER MATL ONLY PLATING CADMIUM & CHROMATE	SCREW,MACHINE
NAS5406U	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS549GL6	02955	LAMIN EPOXY/GLASS	WASHER
NAS549GXXX	02955	LAMIN EPOXY/GLASS	WASHER,NONMETAL
NAS557	99010	NOT TO BE USED ON SHUTTLE	GROMMET,PLASTIC
NAS560HXX-XX	10267	CRES A286 FASTENER MATL ONLY	SCREW,MACHINE
NAS561C	10431	CRES 300 SERIES NON-FREE MACH	PIN,SPRING
NAS561S	10089	CRES 302 COND B BAR AND WIRE	PIN,SPRING
NAS563C	10267	CRES A286 FASTENER MATL ONLY	BOLT,FULL THREAD
NAS564C	10267	CRES A286 FASTENER MATL ONLY	BOLT,FULL THREAD
NAS565C	10267	CRES A286 FASTENER MATL ONLY	BOLT,FULL THREAD
NAS566C	10267	CRES A286 FASTENER MATL ONLY	BOLT,FULL THREAD
NAS567C	10267	CRES A286 FASTENER MATL ONLY	BOLT,FULL THREAD
NAS568C	10267	CRES A286 FASTENER MATL ONLY	BOLT,FULL THREAD
NAS569C	10267	CRES A286 FASTENER MATL ONLY	BOLT,FULL THREAD
NAS571C	10267	CRES A286 FASTENER MATL ONLY	BOLT,FULL THREAD

MSFC-HDBK-527 REV F 9999942 0007148 T

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS572C	10267	CRES A286 FASTENER MATL ONLY	BOLT,FULL THREAD
NAS577-XXA	05723 10114	LUBE DRY STEEL 4340 160-200KSI BAR FRG	NUT,SELF-LOCKING
NAS6000-	50140 30082	CRES A286 160 KSI BAR FRG TBG PLATING CADMIUM & CHROMATE	SCREW,HEX HEAD
NAS6000U	50140	CRES A286 160 KSI BAR FRG TBG	EX HEAD
NAS6001-	50140 30082	CRES A286 160 KSI BAR FRG TBG PLATING CADMIUM & CHROMATE	SCREW,HEX HEAD
NAS6001U	50140	CRES A286 160 KSI BAR FRG TBG	EX HEAD
NAS6002-	50140 30082	CRES A286 160 KSI BAR FRG TBG PLATING CADMIUM & CHROMATE	SCREW,HEX HEAD
NAS6002U	50140	CRES A286 160 KSI BAR FRG TBG	EX HEAD
NAS6003-	50140 30082	CRES A286 160 KSI BAR FRG TBG PLATING CADMIUM & CHROMATE	SCREW,HEX HEAD
NAS6003U	50140	CRES A286 160 KSI BAR FRG TBG	EX HEAD
NAS607-X-X	20223 30104	CTNG CORROSION PREVENTIVE STEEL ALLOY RC47-63	PIN,HEADLESS
NAS607-X-XP	20223 30082 30104	CTNG CORROSION PREVENTIVE PLATING CADMIUM & CHROMATE STEEL ALLOY RC47-63	PIN,HEADLESS
NAS620-XX	30082 10358	PLATING CADMIUM & CHROMATE STEEL SAE/SISI 1008-1010	WASHER,FLAT
NAS620A	10503	AL 5052-H32/H34/H36 SHT & PLT	WASHER,FLAT
NAS620B	10321 30082	BRASS, ALL FORM PLATING CADMIUM & CHROMATE	WASHER,FLAT
NAS620C	10268	CRES 300 SERIES FASTENER MATL	WASHER,FLAT
NAS620CIDL	10268	CRES 300 SERIES FASTENER MATL	WASHER
NAS6303U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6304U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6305U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6306U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6307U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6308U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD

MSFC-HDBK-527 REV F 9999942 0007149 1

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS6309U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6310U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6311U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6312U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6313U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6314U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6315U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6316U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6317U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6318U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6319U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6320U	10267	CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD
NAS6403U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS6404U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS6405U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS6406U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS6407U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS6408U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS6409U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS6410U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS6411U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS6412U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS6413U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS6414U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS6415U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS6416U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS6417U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
6418U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD

MSFC-HDBK-527 REV F 9999942 0007150 8

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS6419U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS6420U	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS662C	10268 30080	CRES 300 SERIES FASTENER MATL CRES 303 FREE MACHINING	SCREW,MACHINE
NAS663	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,FLUSH HEAD
NAS664	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,FLUSH HEAD
NAS665	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,FLUSH HEAD
NAS666	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,FLUSH HEAD
NAS667	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,FLUSH HEAD
NAS668	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,FLUSH HEAD
NAS669	30082 10515	PLATING CADMIUM & CHROMATE STEEL 105501090 LOW CARBON	RING-INTERNAL
NAS6704U	05168 10267 00019	CETYL ALCOHOL,96 PERCENT CRES A286 FASTENER MATL ONLY NYLON PLASTIC	BOLT,HEX HEAD
NAS6705U	05168 10267 00019	CETYL ALCOHOL 96 PERCENT CRES A286 FASTENER MATL ONLY NYLON PLASTIC	BOLT,HEX HEAD
NAS6706U	05168 10267 00019	CETYL ALCOHOL 96 PERCENT CRES A286 FASTENER MATL ONLY NYLON PLASTIC	BOLT,HEX HEAD
NAS6707U	05168 10267 00019	CETYL ALCOHOL 96 PERCENT CRES A286 FASTENER MATL ONLY NYLON PLASTIC	BOLT,HEX HEAD
NAS6708U	05168 10267 00019	CETYL ALCOHOL 96 PERCENT CRES A286 FASTENER MATL ONLY NYLON PLASTIC	BOLT,HEX HEAD
NAS6709U	05168 10267 00019	CETYL ALCOHOL 96 PERCENT CRES A286 FASTENER MATL ONLY NYLON PLASTIC	BOLT,HEX HEAD
NAS6710U	05168 10267 00019	CETYL ALCOHOL 96 PERCENT CRES A286 FASTENER MATL ONLY NYLON PLASTIC	BOLT,HEX HEAD
NAS6711U	05168 10267 00019	CETYL ALCOHOL 96 PERCENT CRES A286 FASTENER MATL ONLY NYLON PLASTIC	BOLT,HEX HEAD
NAS6712U	05168 10267	CETYL ALCOHOL 96 PERCENT CRES A286 FASTENER MATL ONLY	BOLT,HEX HEAD

MSFC-HDBK-527 REV F ■ 9999942 0007151 T ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS6712U	00019	NYLON PLASTIC	BOLT,HEX HEAD
NAS6713U	05168	CETYL ALCOHOL 96 PERCENT	BOLT,HEX HEAD
	10267	CRES A286 FASTENER MATL ONLY	
	00019	NYLON PLASTIC	
NAS6714U	05168	CETYL ALCOHOL 96 PERCENT	BOLT,HEX HEAD
	10267	CRES A286 FASTENER MATL ONLY	
	00019	NYLON PLASTIC	
NAS6715U	05168	CETYL ALCOHOL 96 PERCENT	BOLT,HEX HEAD
	10267	CRES A286 FASTENER MATL ONLY	
	00019	NYLON PLASTIC	
NAS6716U	05168	CETYL ALCOHOL 96 PERCENT	BOLT,HEX HEAD
	10267	CRES A286 FASTENER MATL ONLY	
	00019	NYLON PLASTIC	
NAS6717U	05168	CETYL ALCOHOL 96 PERCENT	BOLT,HEX HEAD
	10267	CRES A286 FASTENER MATL ONLY	
	00019	NYLON PLASTIC	
NAS6718U	05168	CETYL ALCOHOL 96 PERCENT	BOLT,HEX HEAD
	10267	CRES A286 FASTENER MATL ONLY	
	00019	NYLON PLASTIC	
NAS6719U	05168	CETYL ALCOHOL 96 PERCENT	BOLT,HEX HEAD
	10267	CRES A286 FASTENER MATL ONLY	
	00019	NYLON PLASTIC	
NAS671C	30080	CRES 303 FREE MACHINING	NUT,PLAIN, HEX
NAS6720U	05168	CETYL ALCOHOL 96 PERCENT	BOLT,HEX HEAD
	10267	CRES A286 FASTENER MATL ONLY	
	00019	NYLON PLASTIC	
NAS673V	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS674V	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS675V	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS676V	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS677V	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS678V	10365	TI 6AL 4V STA BAR & FORGINGS	BOLT,HEX HEAD
NAS679CXX	10267	CRES A286 FASTENER MATL ONLY	NUT,SELF-LOCKING
	10281	PLATING SILVER,FASTENERS ONLY	
NAS679CXXM	10267	CRES A286 FASTENER MATL ONLY	NUT,SELF-LOCKING
	20247	LUBE DRY ON METALLIC FASTENRS	
NAS686CXXM	10267	CRES A286 FASTENER MATL ONLY	NUT,SELF-LOCKING
	05723	LUBE DRY	

MSFC-HDBK-527 REV F 9999942 0007152 1

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS687CXX	10267 10281	CRES A286 FASTENER MATL ONLY PLATING SILVER,FASTENERS ONLY	NUT PLATE, S/L
NAS6900	10267 30082	CRES A286 FASTENER MATL ONLY PLATING CADMIUM & CHROMATE	SCREW,PAN HEAD
NAS6901	10267 30082	CRES A286 FASTENER MATL ONLY PLATING CADMIUM & CHROMATE	SCREW,PAN HEAD
NAS6902	10267 30082	CRES A286 FASTENER MATL ONLY PLATING CADMIUM & CHROMATE	SCREW,PAN HEAD
NAS6903	10267 30082	CRES A286 FASTENER MATL ONLY PLATING CADMIUM & CHROMATE	SCREW,PAN HEAD
NAS6904	10267 30082	CRES A286 FASTENER MATL ONLY PLATING CADMIUM & CHROMATE	SCREW,PAN HEAD
NAS6905	10267 30082	CRES A286 FASTENER MATL ONLY PLATING CADMIUM & CHROMATE	SCREW,PAN HEAD
NAS6906	10267 30082	CRES A286 FASTENER MATL ONLY PLATING CADMIUM & CHROMATE	SCREW,PAN HEAD
NAS697CX	10267 10281	CRES A286 FASTENER MATL SH PLATING SILVER	NUT
NAS697CXX	10267 10039	CRES A286 FASTENER MATL ONLY PLATING SILVER	NUT,SELF-LOCKING
NAS697CXXM	10267 05723	CRES A286 FASTENER MATL ONLY LUBE DRY	NUT,SELF-LOCKING
NAS699-XX	30105 30112 10368 30099	AL 2014-T6,2024-T6/T851 BAR AL 2024-T3/T4 PLATE BAR TUBE AL 2024-T4 SUNSTRAND LEE PLUG AL 3017 ALL TEMPERS	NUT,CYLINDER LOK
NAS7004H	60059 10267	CETYL ALCOHOL CRES A286 FASTENER MATL ONLY	PIN,SWAGE LOCKNG
NAS7005H	60059 10267	CETYL ALCOHOL CRES A286 FASTENER MATL ONLY	PIN,SWAGE LOCKNG
NAS7006H	60059 10267	CETYL ALCOHOL CRES A286 FASTENER MATL ONLY	PIN,SWAGE LOCKNG
NAS7007H	60059 10267	CETYL ALCOHOL CRES A286 FASTENER MATL ONLY	PIN,SWAGE LOCKNG
NAS7008H	60059 10267	CETYL ALCOHOL CRES A286 FASTENER MATL ONLY	PIN,SWAGE LOCKNG
NAS7009H	60059 10267	CETYL ALCOHOL CRES A286 FASTENER MATL ONLY	PIN,SWAGE LOCKNG

MSFC-HDBK-527 REV F ■ 9999942 0007153 3 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NAS7010H	60059	CETYL ALCOHOL	PIN,SWAGE LOCKNG
	10267	CRES A286 FASTENER MATL ONLY	
NAS7011H	60059	CETYL ALCOHOL	PIN,SWAGE LOCKNG
	10267	CRES A286 FASTENER MATL ONLY	
NAS7012H	60059	CETYL ALCOHOL	PIN,SWAGE LOCKNG
	10267	CRES A286 FASTENER MATL ONLY	
NAS7013H	60059	CETYL ALCOHOL	PIN,SWAGE LOCKNG
	10267	CRES A286 FASTENER MATL ONLY	
NAS7014H	60059	CETYL ALCOHOL	PIN,SWAGE LOCKNG
	10267	CRES A286 FASTENER MATL ONLY	
NAS7015H	60059	CETYL ALCOHOL	PIN,SWAGE LOCKNG
	10267	CRES A286 FASTENER MATL ONLY	
NAS7016H	60059	CETYL ALCOHOL	PIN,SWAGE LOCKNG
	10267	CRES A286 FASTENER MATL ONLY	
NAS7017H	60059	CETYL ALCOHOL	PIN,SWAGE LOCKNG
	10267	CRES A286 FASTENER MATL ONLY	
NAS7018H	60059	CETYL ALCOHOL	PIN,SWAGE LOCKNG
	10267	CRES A286 FASTENER MATL ONLY	
NAS7019H	60059	CETYL ALCOHOL	PIN,SWAGE LOCKNG
	10267	CRES A286 FASTENER MATL ONLY	
NAS7020H	60059	CETYL ALCOHOL	PIN,SWAGE LOCKNG
	10267	CRES A286 FASTENER MATL ONLY	
NAS7021H	60059	CETYL ALCOHOL	PIN,SWAGE LOCKNG
	10267	CRES A286 FASTENER MATL ONLY	
NAS7022H	60059	CETYL ALCOHOL	PIN,SWAGE LOCKNG
	10267	CRES A286 FASTENER MATL ONLY	
NAS70C	10267	CRES A286 FASTENER MATL ONLY	BOLT,FULL THREAD
NAS817-XX	10282	AL 3003 SHT STP PLT FOIL	CAP-PROTECTIVE
NB 10614	10431	CRES 300 SERIES	NUT
NB-CX-XX	30135	AL 2011	CONNECTOR
	10368	AL 2024	
	10396	AL A380	
NB6GEXX P OR T	30135	AL 2011 T3 BAR RODE WIRE	CONNECTOR
	10337	AL 6061-T6	
	10396	AL A380 CASTING	
	10634	ANACONDA 7021 AU PLATED	
	10638	BE-CU ALLOY STRIP	
	10220	CRES 304 ANN WIRE	
	10475	CRES 305 SHT & STP	

MSFC-HDBK-527 REV F 9999942 0007154 5

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NB6GEXX P OR T	50232	CU,PB ANACONDA 129,AU PLATED	CONNECTOR
	10046	PLATING NI ELECTROLESS	
	10079	SOLDER SN 63	
	10149	SPRING BE-CU AT WIRE & STRIP	
	10299	SPRING STL 1095 COND 2 SHT STP	
NBOEXX-XX			CONNECTOR
	10337	AL 6061/T6	
	50232	ANACONDA 129 AU PLATED	
	10634	ANACONDA 7021 AU PLATED	
	10638	BE-CU	
	30080	CRES 303	
	10475	CRES 305	
NBOEXX-XXXXX	10337	AL 6061-T6	CONNECTOR
	10047	AL 7075	
	50170	BERYLLIUM COPPER	
	10634	COPPER LEADED NICKEL 7021	
	30080	CRES 303	
	10475	CRES 305	
NBXGEXX	10634	ANACONDA 7021 GOLD PLATED	CONNECTOR
	10475	CRES 305	
	50232	CU PB ANACONDA 129 AU PLATED	
ND112-0001-0505	10267	A286 CRES	SCREW
ND112-0001-0509	10267	CRES A286	SCREW
NDS 1291C	10267	CRES A286 FASTENER MATL SH	NUT
	10281	PLATING SILVER	
NF15000S	30080	CRES 303 FREE MACHINING	
NFL 21201	30099	AL 2017	RIVET
NFL 21215	30099	AL 2017	RIVET
NFL 21217	30099	AL 2017	RIVET
NFL 21218	30099	AL 2017	RIVET
NFL 22201CF	10011	CRES A286	BOLT
NFL 22201TK	10069	TI 6AL 4V	BOLT
NFL 22208 LF	10011	CRES A286	BOLT
NFL 22220	05886	LUBE DRY MOLYKOTE 106 M052	BOLT
	10069	TI 6AL 4V	
NFL 22258	30120	CRES 431	BOLT
NFL 22259	30120	CRES 431	BOLT

MSFC-HDBK-527 REV F 9999942 0007155 7

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NFL 22275 TK	05886	DRY LUBE MOLYCOTE X-106	BOLT , ROUND HEAD
	10069	TI 6AL 4V	
NFL 22275CF	30120	CRES 431	BOLT , ROUND HEAD
NFL 22500	10124	CRES A286	NUT , ANCHOR
	10281	SILVER PLATING	
NFL 22541	10124	CRES A286	NUT , HEX-HEAD
	10281	SILVER PLATING	
NFL 22551	10124	CRES A286	NUT , ANCHOR
	10039	SILVER PLATING	
NFL 22552	10124	CRES A286	NUT , ANCHOR
	10039	SILVER PLATING	
NFL 22561	10124	CRES A286	NUT
	10039	SILVER PLATING	
NFL 22562	10124	CRES A286	NUT, ANCHOR
	10039	SILVER PLATING	
NFL 22587	10124	CRES A286	NUT
	10039	SILVER PLATING	
NFL 22588	10124	CRES A286	NUT
	10039	SILVER PLATING	
NFL 22595	10124	CRES A286	NUT
	10039	SILVER PLATE	
NFL 22596	10124	CRES A286	ANCHOR NUT
	10039	SILVER PLATING	
NFL 23111 CA	10090	CRES 304L	WASHER
NFL 23111 DG	50055	AL 2024	WASHER
NFL 23112 CA	10090	CRES 304L	WASHER
NFL 23112 DG	50055	AL 2024	WASHER
NFL 23116 CA	10090	CRES 304L	WASHER
NFL 23116 DG	50055	AL 2024	WASHER
NFL 23118	50503	CRES 420	WASHER
NH1003XXX	10466	AL 2219-T42 RIVETS	
	10022	AL 6061-T6/62/651 SHT & PLT	
	10023	AL 6061-T6/651 RLD BAR SHP ROD	
	10024	AL 6061-T6/T6511 EXT BR SHP TB	
	10321	BRASS, ALL FORM	
	10276	COATING ANODIC TYPE 1	
	416	CTNG CONVERSION BL OXIDE	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NLS-R-10	10024	AL 6061-T6	CLAMP , STRAIN RELIEF
NLS-R-8	10024	AL 6061-T6	CLAMP , STRAIN RELIEF
NLS-RPC-XX	10023	AL 6061-T6	CONNECTOR
	10606	CRES 18-8	
	10382	CRES 302	
	10351	CRES 304	
	10046	PLATING NI ELECTROLESS	
NLS-S-XX	10171	AL 5052 CLAMP-CABLE	CONNECTOR
	10396	AL A380 ENDBELL/FOLLOWER	
	10262	CRES 302 SCREW/WASHER	
	10046	PLATING NI ELECTROLESS	
NLS6GTXX-XX	10337	AL 6061 BARREL	CONNECTOR
	10048	AL 7075	
	10634	ANACONDA 7021 AU PLATE	
	10475	CRES 305	
	10638	E-CU	
	30142	SPRING STEEL	
NLSOEXX-XXXX	30135	AL 2011	CONNECTOR
	10337	AL 6061	
	10396	AL A380	
	10271	BERYLLIUM COPPER	
	10634	COPPER LEADED NICKEL 7021	
	30080	CRES 303	
	10475	CRES 305	
NO.7 ZIPPER	02961	ZIPPER BRASS/COTTON	
NR 10614	10431	CRES 300 SERIES	NUT 10-32
NR 10615	10431	CRES 300 SERIES	NUT 25-28
NR 10622	10431	CRES 300 SERIES	WASHER
NR 10625	10431	CRES 300 SERIES	TERMINALS-LOCKING
NR 110	60069	PTFE	BUSHING
NR 22-2001	05543	LAMIN GLASS-EPOXY NEMA FR-4	WASHER,SHOULDER
NR 432202021760	10697	MAGNETIC STL IRON BASE 1.5% SI	CORE
NR 432202036630	10697	MAGNETIC STL IRON BASE 1.5% SI	CORE
NR 432202130300	10697	MAGNETIC STL IRON BASE 1.5% SI	COIL-FORM
NR. 308	10351	CRES 304	HANDGRIP
NS103606	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	

MSFC-HDBK-527 REV F 9999942 0007157 0

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
NS103620	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
NS103623	10267	CRES A286 FASTENER MATL ONLY	
	05520	LUBE DRY TIO LUBE 460 MS21063	
	10281	PLATING SILVER,FASTENERS ONLY	
NS103700	10267	CRES A286 FASTENER MATL ONLY	
	00597	LUBE DRY	
	10424	NI STA INCO 718 FASTENERS ONLY	
NS103741	10267	CRES A286 FASTENER MATL ONLY	
NS103987	10475	CRES 305 SHEET & STRIP	
	10267	CRES A286 FASTENER MATL ONLY	
	10354	CU WIRE ELECTRICAL CONDUCTORS	
	10281	PLATING SILVER,FASTENERS ONLY	
NS202005	10267	CRES A286 FASTENER MATL ONLY	
NS202007	10267	CRES A286 FASTENER MATL ONLY	
NS202014	10292	AL 2024-T6 BAR ROD & WIRE	
	00666	CTNG CONVERSION CHROMATE INORG	
NS202070	10088	CRES 301 ANN THRU 1/2 HD PT SH	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER, FASTENERS ONLY	
NS202092	10267	CRES A286 FASTENER MATL ONLY	
NS202115	10267	CRES A286 FASTENER MATL ONLY	
NS202286	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
NS202426	10267	CRES A286 FASTENER MATL ONLY	
NS3055	10292	AL 2024-T6 BAR ROD & WIRE	
	10276	COATING ANODIC TYPE 1	
NS90234	10090	CRES 304 ANN SHT PLT STRIP	
NS90338	10090	CRES 304 ANN SHT PLT STRIP	
NS90339	10090	CRES 304 ANN SHT PLT STRIP	
NS90444	10090	CRES 304 ANN SHT PLT STRIP	
NS90945	10090	CRES 304 ANN SHT PLT STRIP	
NS90946	10090	CRES 304 ANN SHT PLT STRIP	
NW4-2813	00019	NYLON PLASTIC	WASHER

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
OJR-217B	10275	PLATING CHROMIUM (CLASS 2)	
	10648	STEEL 1008-1020	
OK,MJOL	06308	POLYCARBONATE NO 1663 AMBER	
P1100-24N	10321	BRASS, ALL FORM	
P1329-X	10321	BRASS, ALL FORM	
P1362-X	10321	BRASS, ALL FORM	
PAC1037	05091	ADHES AF-143/EC3917 EPOXY FILM	
	05127	ADHES FM 400/BR400 EPOX FILM	
	05092	ADHES FOAM METLBOND 6607 EPOXY	
	10022	AL 6061-T6/62/651 SHT & PLT	
	05007	CORE AL ALLOY HC ADH BONDED	
PAN 3027	10097	CRES 321	SCREW
PAN 3036	10069	TI 6AL 4V	BOLT
PAN 3037	05886	DRY LUBE MOLYCOTE X-106	BOLT , HEX
	10069	TI 6AL 4V	
PAN 3038	10069	TI 6AL 4V	BOLT
PAN 3039	10069	TI 6AL 4V	BOLT
PAN 3056	10124	CRES A286	NUT
PAN 3057	10069	TI 6AL 4V	SCREW
PAN 3114	10124	CRES A286	NUT
PAN 3118	10606	CRES 18/8	NUT
PAN 3120	10124	CRES A286	NUT
PAN 3350 TYPE A	10292	AL 2024-T6	COLLAR
	10277	CTNG ANODIC	
PAN 3825	30108	2024-T4	INSERT , BLIND
	10276	CTNG ANODIC	
PAN 3827	30108	AL 2024-T4	INSERT
	10276	CTNG ANODIC	
PAN 3828	30111	AL 2024-T4	INSERT
	10527	CTNG ANOD	
PAN 4838	10097	CRES 321	BUSHING
PB3-1/2	30082	PLATING CADMIUM & CHROMATE	
	10232	SPRING STEEL MUSIC WIRE	

MSFC-HDBK-527 REV F 9999942 0007159 4

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
PBF1295	10268	CRES 300 SERIES FASTENER MATL	
PBI	05950	FABRIC PBI S-164FX RASCHEL NET	
	05506	THREAD PBI POLYBENZIMIDAZOLE	
PD-120	60149	POLYETHYLENE	CAPLUG
PL. NR. 72	10321	BRASS	SOLDER TERMINAL
PLGAR 70020	50066	CRES 416	PLUG
PLT210	05168	CETYL ALCOHOL 96 PERCENT	
	10506	CRES 303/304 BAR AND WIRE	
	20026	LAURIC ACID	
	20028	LUBE DRY DAG 250 ORGANIC BINDR	
	05303	LUBE DRY EVERLUBE 1120-8	
	20027	PARAFFIN WAX	
	30082	PLATING CADMIUM & CHROMATE	
	10109	STEEL 4130 125-180KSI BAR FRG	
PLT220	10267	CRES A286 FASTENER MATL ONLY	
	20026	LAURIC ACID	
	20028	LUBE DRY DAG 250 ORGANIC BINDR	
	05303	LUBE DRY EVERLUBE 1120-8	
	20027	PARAFFIN WAX	
PM788	10321	BRASS, ALL FORM	
	10328	PLATING GOLD	
PN 31270	10248	CU FLAT RODS & SHAPES	CABLE SHOE
	10501	CU RODS & SHAPES	
	10483	CU SEAMLESS TUBING	
	10445	PLATING TIN	
PR3 1/2	10024	AL 6061-T6/T6511 EXT BR SHP TB	
	10296	SPRING 316 COND B WIRE	
Q13645-X	00016	TEFLON TFE	
R-1600-7.5 OA	10046	PLATING NI ELECTROLESS	
	10513	STEEL 4XXX/8XXX OVER 220 KSI	
R0014042-3	00016	TFE TEFLON	GUIDE
R0014043	10098	CRES 304	SPACER
R21240CC	10351	CRES 304 ANN BAR SHP FRG WIRE	2.00
	00016	TEFLON TFE	
R21813CC	10351	CRES 304 ANN BAR SHP FRG WIRE	
	00016	TEFLON TFE	
R3800CC-X-XXXX	10381	CRES 304L/316L/321/347 ANN SHT	
	00016	TEFLON TFE	

MSFC-HDBK-527 REV F ■ 9999942 0007160 0 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
R44 117	10693	CRES 17-4 PH H 1075	CAP ASSEMBLY DYNATUBE
R44 239	10693	CRES 17-4 PH H 1075	CONNECTOR DYNATUBE
R44102PF	10430	CRES 17-4PH H1075	CONNECTOR
R44111N	10384	NI INCO 718 ST/STA BAR	TEE,DYNATUBE
R44111P	10430	CRES 17-4PH H1075 BR (RES266)	TEE,DYNATUBE
R44118NN	10406	NI INCO 718 1750 STA BAR & FRG	JAM NUT,DYNATUBE
R44118PN	10430	CRES 17-4PH H1075 BR (RES266)	JAM NUT,DYNATUBE
R44118T-	05158 10401	LUBE DRY EVERLUBE 620A TI 6AL 4V STA BAR/FRG (RES143)	JAM NUT,DYNATUBE
R44129-90P	10430 10089	CRES 17-4PH H1075 BR (RES266) CRES 302 COND B BAR AND WIRE	DYNATUBE ASSY
R44132	10430	CRES 17-4DH H1075	TEE DYNATUBE
R44151	10693	CRES 17-4 PH H1075	CONNECTOR DYNATUBE
R44182P	10430	CRES 17-4PH H1075 BR (RES266)	CONNECTOR,DYNATU
R44275PT	10430 05158 10401	CRES 17-4PH H1075 BR (RES266) LUBE DRY EVERLUBE 620A TI 6AL 4V STA BAR/FRG (RES143)	
R44280	10074 10406	CRES 17-4DH H1075 NI INCONEL 718	FITTING ASSY DYNATUBE
R44285PT	10430	CRES 17-4PH H1075 BR (RES266)	
R44358	10430	CRES 17-4PH H1075	CONNECTOR DYNATUBE
R44653	10430	CRES 17-4PH H1075	FITTING,TEE,REDUCER
R45116T	10069	TI 6AL 4V	REDUCER
R45118	10430	CRES 17-4PH H1075	CONNECTOR DYNATUBE
R4650	10090	CRES 304	HOUSING , RECEPTACLE
R50200CC-6-0120	10351 00016	CRES 304 ANN BAR SHP FRG WIRE TEFLON TFE	
RD111-1009-3412	10267 10267 05167	CRES A286 CRES A286 DRY FILM LUBE	HEX HEAD BOLT
RD111-1010-3338	00597 10267 10267	DRY FILM LUBE INCO 718 INCO 718	BOLT

MSFC-HDBK-527 REV F ■ 9999942 0007161 2 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
RD111-1010-3358	10267	CRES A286	BOLT
	05167	DRY FILM COATED	
RD111-1011	10267	CRES A286 FASTENER MATL ONLY	BOLT, HEX HEAD
RD111-1011-3XXX	10267	A286 CRES	BOLT-HEX HEAD
	10267	A286 CRES	
	00597	MOLYBDENUM DISULFIED	
RD111-1012	10267	CRES A286 FASTENER MATL ONLY	BOLT, HEX HEAD
RD111-1012-0306	10267	CRES A286	
	10281	SILVER PLATE	
RD111-1012-0407	10267	CRES A286	BOLT
RD111-1012-3XXX	10267	A286 CRES	BOLT-HEX HEAD
	10267	A286 CRES	
	00597	MOLYBDENUM DISULFIED	
RD111-1016-3402	10267	CRES A286	BOLT
	05167	DRY FILM LUBE	
	10281	SILVER PLATE	
RD111-1016-6402	10267	CRES A286	BOLT
	05167	DRY FILM LUBE	
	10281	SILVER PLATE	
RD111-3003-5302	10267	A286 CRES	
	10267	A286 CRES	
	05046	MOLYBDENUM DISULFIDE	
RD111-4008	10267	CRES A286 FASTENER MATL ONLY	BOLT,EXTR WRENCH
RD111-4008-6414	10267	A286 CRES	BOLT,EXT WRENCH
	10267	A286 CRES	
	00597	MOLYBDENUM DISULFIDE	
RD111-4008-6XXX	10267	A286 CRES	BOLT
	10267	A286 CRES	
	00597	DRY FILM COAT	
RD111 4008-7XXX	10267	A286 CRES	BOLT
	10267	A286 CRES	
	00597	DRY FILM COAT	
RD111-4009	10267	CRES A286 FASTENER MATL ONLY	BOLT,EXTR WRENCH
RD111-4009-0308	10267	CRES A286	BOLT
	05167	DRYFILM	
RD111-4009-6446	10267	CRES A286	BOLT
	05167	DRY FILM LUBE	
RD111-4009-6XXX	10267	A286 CRES	BOLT,EXT WRENCH
	10267	A286 CRES	

MSFC-HDBK-527 REV F 9999942 0007162 4

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
RD111-4009-6XXX	05046	MOLYBDENUM DISULFIDE	BOLT,EXT WRENCH
RD111-4010-0XXX	10267 10281	A286 CRES SILVER PLATE	BOLT
RD111-4010-3XXX	10267 00597 00597	CRES A286 DRY FILM COAT DRY FILM LUBE	BOLT
RD111-4010-4XXX	10267 10267 00597	A286 CRES A286 CRES DRY FILM COAT	BOLT
RD111-4011-3XXX	10267 10267 00597	A286 CRES A286 CRES DRY FILM LUBE	BOLT
RD111-4011-4XXX	10267 10267 00597	A286 CRES A286 CRES DRY FILM LUBE	BOLT
RD111-4022-XXXX	10267 00597	A286 CRES DRY LUBE	BOLT
RD111-4100-XXXX	10267 00597	A286 CRES MOLYBDENUM DISULFIDE	BOLT
RD111-4102-3XXX	10267 00597	A286 CRES DRY FILM LUBE	BOLT SPLINE DRIVE
RD111-4102-4XXX	00597 10424	DRY FILM COATED INCO 718	BOLT
RD111-4103-3XXX	00597 10424	DRY FILM INCO 718	BOLT
RD111-4103-4XXX	00597 10424	DRY FILM INCO 718	BOLT
RD111-4104-34XX	10267 00597	A286 CRES DRY FILM LUBE	BOLT
RD111-4104-3XXX	10267 00597	A286 CRES MOLYBDENUM DISULFIDE	BOLT-EXTERN WRENCH
RD111-4105-3XXX	00597 10424	DRY FILM COAT INCONEL 718	BOLT
RD111-8010-XXXX	10267 10424 00597 30125	A286 CRES INCO 718 MOLYBDENUM DISULFIDE WASPALLOY	NUT SELF LOCKING
RD111-9003-0012	10267 05167	CRES A286 DRY FILM COATED	BOLT

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
RD111-9003-0019	10267	CRES A286	BOLT
	05167	DRY FILM COAT	
RD111-9004-0018	10267	CRES A286	BOLT
	05167	DRY FILM LUBE	
RD112-5001-1008	10267	CRES A286	SCREW
	05167	DRY FILM LUBE	
RD112-5001-1010	10267	CRES A286	SCREW
	05167	DRY FILM COAT	
RD112-5007-1710	10267	CRES A286	SCREW
	05167	DRY FILM COATED	
RD112-5007-2609	10267	CRES A286	SCREW
	05167	DRY FILM COATED	
RD112-5007-2612	10267	CRES A286	SCREW
	05167	DRY FILM COAT	
RD112-5007-2710	10267	CRES A286	SCREW
	05167	DRY FILM COATED	
RD112-5007-XXXX	10267	CRES A286	SCREW
	00597	DRY FILM COAT	
RD112-5009	10268	CRES 300 SERIES	SCREW
RD112-5011-0XXX	10315	320 CRES	SCREW
RD113-3002-0531	05167	DRY FILM COAT	STUD
	10424	INCONEL 718	
RD114-1019-003	10267	CRES A286	NUT
RD114-8003-1003	10267	CRES A286	NUT
	10281	SILVER PLATE	
RD114-8003-2XXX	10267	A286 CRES	NUT-SELF LOCKING
	10267	A286 CRES	
	10267	A286 CRES	
	00597	DRY FILM LUBE	
RD114-8005-1XXX	10267	CRES A286 FASTENER MATL ONLY	NUT,SELF-LOCKING
	10281	PLATING SILVER,FASTENERS ONLY	
RD114-8005-2XXX	10267	CRES A286	NUT SELF LOCKING
	05167	DRY FILM LUBE	
RD114-8010-0XXX	10267	CRES A286	NUT
	05167	DRY FILM COATED	
	30125	WASP ALLOY	
RD114-8010-XXXX	10267	A286 CRES	SELF LOCKING NUT
	00597	DRY FILM LUBE	

MSFC-HDBK-527 REV F ■ 9999942 0007164 8 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
RD124-8010-XXXX	30125	WASPALLOY	SELF LOCKING NUT
RD122-3003-0305	10315	CRES 302	PIN DOWEL
RD122-3003-XXXX	10296	CRES 302	DOWEL PIN
	10296	CRES 302	
RD122-3004-0704	10390	CRES 347	PIN
RD127-1004-000X	05223	GLASS FABRIC-EPOXY	CLAMP
RD127-1007-00XX	05223	GLASS FABRIC-EPOXY	CLAMP
RD127-2003-1XXX	10097	321 CRES	CLAMP
	10097	321 CRES	
	10099	347 CRES	
	10099	347 CRES	
	05098	SILICONE RUBBER GLASS FABRIC	
RD127-7011-0001	10097	321 CRES	CLAMP
	05098	FIBERGLASS-SILASTIC	
RD153-1002	10267	CRES A286 FASTENER MATL ONLY	WASHER,FLAT
RD153-1003	10099	CRES 347 SERIES	WASHER
RD153-1004-XXXX	10088	301 CRES	
	10294	302 CRES	
RD153-3003	10294	CRES 302 ANN THRU 1/2 HD PT SH	WASHER,CONICAL
RD153-3003-1002	10294	CRES 302	WASHER
RD153-5002	10267	CRES A286 FASTENER MATL ONLY	WASHER,CNTRSUNK
RD153-5002-1003	10267	CRES A286	WASHER
RD153-5002-XXXX	10267	A286 CRES	WASHER
	10267	A286 CRES	
RD153-5006-0005	10424	INCONEL 718	WASHER
	10424	INCONEL 718	
RD153-5006-0006	10424	INCO 718	WASHER
RD153-5007-XXXX	10424	INCO 718	WASHER FLAT
	10424	INCO 718	
RD153-5009-0XXX	10424	INCO 718	WASHER
	10424	INCO 718	
RD153-5009-1001	60377	DYKEM RED STAIN DL	WASHER
	10424	INCO 718	
	10424	INCONEL 718	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
RD171-1041-1002	10348	AL 11XX FOIL	PLATE
	10276	ANODIZE	
RD171-1056-XXXX	10348	1UXX AL FOIL	PLATE ID COMPONENT
	60377	BLUE INK	
RD171-1073-0001	10348	AL 11XX	NAMEPLATE
RD171-4012-0001	10294	CRES 302	TAG
RD171-4015-1001	10294	CRES 302	TAG
RD171-4016-0XXX	10279	AL 1100	TAG
RD171-4016-1001	10279	AL 1100	TAG
RD172-0024-0001	60377	COLOR	TAPE
	05241	TAPE MYLAR/ACRYLIC PS ADHESIVE	
RD172-0025-0001	60377	COLOR	TAPE
	05241	TAPE MYLAR/ACRYLIC PS ADHESIVE	
RD172-0025-XXXX	60377	COLORS	TAPE-ROCKET OX SYS
	05241	TAPE	
RD172-0027-0001	60377	COLOR	TAPE
	05241	TAPE MYLAR/ACRYLIC PS ADHESIVE	
RD172-0029-0001	60377	COLOR	TAPE
	05241	TAPE MYLAR/ACRYLIC PS ADHESIVE	
RD172-0034-0005	60377	COLOR	TAPE
	05241	TAPE MYLAR/ACRYLIC PS ADHESIVE	
RD172-0034-0017	60377	COLOR	TAPE
	05241	TAPE MYLAR/ACRYLIC PS ADHESIVE	
RD172-0034-0018	60377	COLOR	TAPE
	05241	TAPE MYLAR/ACRYLIC PS ADHESIVE	
RD172-0034-0019	60377	COLOR	TAPE
	05241	TAPE MYLAR/ACRYLIC PS ADHESIVE	
RD172-0034-0020	60377	COLOR	TAPE
	05241	TAPE MYLAR/ACRYLIC PS ADHESIVE	
RD172-0034-0025	60377	COLOR	TAPE
	05241	TAPE MYLAR/ACRYLIC PS ADHESIVE	
RD172-0034-0040	60377	COLOR	TAPE
	05241	TAPE MYLAR/ACRYLIC PS ADHESIVE	
RD172-0034-XXXX	60377	COLORS	TAPE-SPECIFIC CONTE
	05241	TAPE	

MSFC-HDBK-527 REV F 9999942 0007166 1

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
RD172-0035-0001	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0035-0002	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0035-XXXX	60377 05241	COLORS TAPE	TAPE-DIRECTION FLOW
RD172-0036-0005	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-0150	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-0155	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-0250	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-0270	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-0600	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-0625	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-0655	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-0750	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-0800	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-1000	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-3500	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-4200	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-4300	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-4446	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-4665	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
RD172-0036-5000	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-5400	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-6100	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-7000	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-7700	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-7800	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-8720	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0036-XXXX	60377 05241	COLORS TAPE	TAPE-PRESSURE DESIG
RD172-0038-0002	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD172-0038-0004	60377 05241	COLOR TAPE MYLAR/ACRYLIC PS ADHESIVE	TAPE
RD261-3014-0XXX	10407 10039	INCO 718 SILVER PLATE	SEAL
RD261-3015-0XXX	10407 10039	INCO 718 SILVER PLATE	SEAL
RD261-3016-XXXX	10407 10039	INCO 718 SILVER PLATE	SEAL
RD261-3017-0XXX	10406 10039	INCO 718 SILVER PLATING	SEAL
RD261-3017-XXXX	10406 10039	INCO 718 SILVER PLATE	SEAL HOT GAS
RD261-3019-XXXX	10384 10039	INCO 718 SILVER PLATE	SEAL
RD265-3017-0XXX	10099	347 CRES	PLUG
RD265-5017	00016	TEFLON TFE	CAP,PORT PLUG
RD265-5017-XXXX	00578 02151	FEP TEFLON TFE TEFLON	CAP

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
RD273-6004-000X	10011	A286 CRES	PLUG
RE113-3001-0525	00597	DRY FILM LUBE	STUD
	10424	INCO 718	
RE113-3001-0531	05072	DRY FILM COATED	STUD
	10424	INCONEL 718	
RE113-3002-0531	05072	DRY FILM COATED	STUD
	10424	INCONEL 718	
RE113-3003-32XX	10424	INCO 718	STUD STRAIGHT
	00597	MOLYBDENUM DISULFIDE	
RE113-3005-0734	10148	CRES 302	STUD
	05167	DRY FILM LUBE	
	10424	INCO 718	
RE127-2006-XXXX	10390	321/347 CRES	CLAMP, CUSHIONED
	02997	FIBERGLASS-SILACAST	
RE127-2011-1XXX	10431	321 CRES	CLAMP,SADDLE
RE127-2012-1XXX	10097	321 CRES	CLAMP
	10097	321 CRES	
RE127-2013-XXXX	10097	321 CRES	CLAMP
	10097	321 CRES	
	02997	FIBERGLASS-SILASTIC	
RE127-2014-XXXX	10097	321 CRES	CLAMP
	10097	321 CRES	
	02997	FIBERGLASS-SILASTIC	
RE127-2015-XXXX	10097	321 CRES	CLAMP
	10097	321 CRES	
	02997	FIBERGLASS-SILASTIC	
RE127-2016-XXXX	10097	321 CRES	CLAMP
	10097	321 CRES	
	02997	FIBERGLASS-SILASTIC	
RE127-2018-XXXX	10097	321 CRES	CLAMP
	10097	321 CRES	
	02997	FIBERGLASS-SILASTIC	
RE251-4301-5702	10506	CRES 300 SERIES	ORIFICE
RE261-3005-1XXX	10011	A286 CRES	SEAL
	10328	GOLD PLATE	
RE483-3001-2149	10321	BRASS	FERRULE
	10312	PLATING TIN	
RE483-3001-2194	10321	BRASS	FERRULE
	10312	PLATING TIN	

MSFC-HDBK-527 REV F 9999942 0007169 7

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
RE483-3001-2250	10321 10312	BRASS PLATING TIN	FERRULE
RE483-3001-2261	10321 10312	BRASS PLATING TIN	FERRULE
RE483-3001-2312	10321 10312	BRASS PLATING TIN	FERRULE
RE483-3002-2232	50111 10312	CU ALLOY PLATING TIN	FERRULE
RE483-3002-2261	50111 10312	CU ALLOY PLATING TIN	FERRULE
RE483-3002-2297	50111 10312	CU ALLOY PLATING TIN	FERRULE
RE483-3002-2327	50111 10312	CU ALLOY PLATING TIN	FERRULE
RE483-3002-2359	50111 10312	CU ALLOY PLATING TIN	FERRULE
RE483-3002-2405	50111 10312	CU ALLOY PLATING TIN	FERRULE
RE483-3003-0430	10321 10312	BRASS PLATING TIN	RING
RE483-3003-0550	10321 10312	BRASS PLATING TIN	RING
RE483-3003-0810	10321 10312	BRASS PLATING TIN	RING
RE483-3003-0920	10321 10312	BRASS PLATING TIN	RING
RE483-3005-0590	50111 10312	CU ALLOY PLATING TIN	RING
RE483-3005-0710	50111 10312	CU ALLOY PLATING TIN	RING
RE483-3005-0719	50111 10312	CU ALLOY PLATING TIN	RING
RE483-3005-1010	50111 10312	CU ALLOY PLATING TIN	RING
RE483-3005-1130	50111 10312	CU ALLOY PLATING TIN	RING
RE483-3007-0438	10670 10276	AL 6061 ANODIC COATING TYPE 1	FERRULE

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
RE483-3007-0469	10670	AL 6061	FERRULE
	10276	ANODIC COATING TYPE 1	
RE483-3007-0562	10670	AL 6061	FERRULE
	10276	ANODIC COATING TYPE 1	
RE433-3007-0594	10670	AL 6061	FERRULE
	10276	ANODIC COATING TYPE 1	
RE483-3007-0719	10670	AL 6061	FERRULE
	10276	ANODIC COATING TYPE 1	
RE483-3007-0844	10670	AL 6061	FERRULE
	10276	ANODIC COATING TYPE 1	
RE483-3007-0938	10670	AL 6061	FERRULE
	10276	ANODIC COATING TYPE 1	
RE483-3007-1000	10670	AL 6061	FERRULE
	10276	ANODIC COATING TYPE 1	
RE483-3007-1125	10670	AL 6061	FERRULE
	10276	ANODIC COATING TYPE 1	
RE483-3007-1156	10670	AL 6061	FERRULE
	10276	ANODIC COATING TYPE 1	
REP4M6	10088	CRES 301 ANN THRU 1/2 HD PT SH	
	20033	GREASE MOBILE #28	
	30082	PLATING CADMIUM & CHROMATE	
	10109	STEEL 4130 125-180 KSI BAR&FRG	
	10107	STEEL 52100 RC 55 BAR	
	00016	TEFLON TFE	
RG142B/U	10354	CU WIRE ELECTRICAL CONDUCTOR	CABLE,COAXIAL
	05417	INSUL CABLE COAXIAL TFE/FEP	
	10039	PLATING SILVER	
RI3039	10148	SPRING 302 COND B WIRE	
RL5008-22E0272	10125	CRES A286 140KSI BAR & FORGING	
RS008846	10452	NI INCO 718 CASTING 1900 ST	
	10281	PLATING SILVER,FASTENERS ONLY	
RS008847	10321	BRASS, ALL FORM	
	10452	NI INCO 718 CASTING 1900 ST	
	10281	PLATING SILVER,FASTENERS ONLY	
RS008850	10022	AL 6061-T6/62/651 SHT & PLT	
	10277	COATING ANODIC TYPE 2	
	05005	RUBBER VITON FLUID RESISTANT	
RT-1146-X/X	05202	BOOT VITON HEAT SHRINK	

MSFC-HDBK-527 REV F 9999942 0007171 5

Information Handling Services, 2000

DATE: 12/23/88
STANDARD COMMERCIAL PARTS

MATERIALS SELECTION LIST FOR SPACE HARDWARE SYSTEMS
MSFC HANDBOOK 527F / JSC 09604F

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
RT-501	20035	TUBING RT-510 HST NEOPRENE	
S 4650	30080	CRES 303	STUD
S-311-P-4/5	10321	BRASS, ALL FORM	
	10322	BRONZE PHOSPHOR,ALL FORMS	
	10328	PLATING GOLD	
S12562	60375	CERAMIC-FILLED TFE	CHANNEL SEAL
S12563	60375	CERAMIC FILLED TEFLON	CHANNEL SEAL
S13076	60375	CERAMIC-FILLED TFE	CHANNEL SEAL
S13077	60375	CERAMIC FILLED TFE	CHANNEL SEAL
S13077-221	60375	FILLED TEFLON CERAMIC	CHANNEL SEAL
S13077-326	60375	FILLED CERAMIC TEFLON	CHANNEL SEAL
S3051-10	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-11	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-12	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-13	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-14	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-15	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-16	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-17	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-18	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
S3051-19	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-20	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-21	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-22	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-23	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-24	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-25	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-26	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-27	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-28	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-29	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-30	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-31	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-32	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	

MSFC-HDBK-527 REV F 9999942 0007173 9

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
S3051-33	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-34	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-35	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-36	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-37	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-38	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-39	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-4	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
	01883	LAMIN GLASS/SILICONE	
S3051-40	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-5	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
	01883	LAMIN GLASS/SILICONE	
S3051-6	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
	01883	LAMIN GLASS/SILICONE	
S3051-8	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3051-9	30111	AL 2024-T3/T4 SHEET	
	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
S3052-X	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	

MSFC-HDBK-527 REV F 9999942 0007174 0

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
S3551-4	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
	01883	LAMIN GLASS/SILICONE	
S3551-5	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
	01883	LAMIN GLASS/SILICONE	
S3551-6	10003	AL 2024-T851/T6/T62 BR RD WR	
	10277	COATING ANODIC TYPE 2	
	01883	LAMIN GLASS/SILICONE	
S4931920	10069	TI 6AL 4V	RIVET
S9094B	10515	STEEL 1055-1090 LOW CARBON	
	10731	STEEL AISI 1340	
	10630	STEEL LEDLOY-A	
	10295	TI 6AL 6V 2SN ANN BAR BLT FRG	
SA-5	05298	NYLON 6/6	
SA-6	05298	NYLON 6/6	
SB1050	20058	TAPE SB 1050Y STRETCH SILICONE	
SF 5005	10124	CRES A286	NUT
	10039	SILVER PLATED	
SF 6005	10124	CRES A286	NUT ANCHOR
SF9-4592	05005	RUBBER VITON FLUID RESISTANT	
SL 10 STR	50207	MTL UNIDENTIFIED	BALL BEARING
SL-10-XX	10469	CU WIRE / AG PLATED	WIRE
	01342	KAPTON INSULATION	
SL0230010N	10046	PLATING NI ELECTROLESS	
	10358	STEEL SAE/AISI 1008-1010	
SL4001-10	10089	CRES 302 COND B BAR AND WIRE	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
SL4001-11	10089	CRES 302 COND B BAR AND WIRE	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
SL4001-12	10089	CRES 302 COND B BAR AND WIRE	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
SL4001-14	10089	CRES 302 COND B BAR AND WIRE	
	10384	NI INCO 718 ST/STA BAR	
	10281	PLATING SILVER,FASTENERS ONLY	

MSFC-HDBK-527 REV F ■ 9999942 0007175 2 ■

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
SL4001-15	10089	CRES 302 COND B BAR AND WIRE	
	10384	NI INCO 718 ST/STA BAR	
	10281	PLATING SILVER,FASTENERS ONLY	
SL4001-16	10089	CRES 302 COND B BAR AND WIRE	
	10384	NI INCO 718 ST/STA BAR	
	10281	PLATING SILVER,FASTENERS ONLY	
SL4001-17	10089	CRES 302 COND B BAR AND WIRE	
	10384	NI INCO 718 ST/STA BAR	
	10281	PLATING SILVER,FASTENERS ONLY	
SL4001-18	10089	CRES 302 COND B BAR AND WIRE	
	10384	NI INCO 718 ST/STA BAR	
	10281	PLATING SILVER,FASTENERS ONLY	
SL4001-19	10089	CRES 302 COND B BAR AND WIRE	
	10384	NI INCO 718 ST/STA BAR	
	10281	PLATING SILVER,FASTENERS ONLY	
SL4001-20	10089	CRES 302 COND B BAR AND WIRE	
	10384	NI INCO 718 ST/STA BAR	
	10281	PLATING SILVER,FASTENERS ONLY	
SL4001-4	10089	CRES 302 COND B BAR AND WIRE	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
SL4001-5	10089	CRES 302 COND B BAR AND WIRE	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
SL4001-6	10089	CRES 302 COND B BAR AND WIRE	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
SL4001-7	10089	CRES 302 COND B BAR AND WIRE	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
SL4001-8	10089	CRES 302 COND B BAR AND WIRE	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
SL4001-9	10089	CRES 302 COND B BAR AND WIRE	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
SL5-X-XXC	10268	CRES 300 SERIES FASTENER MATL	
SL601-XX-CS	30080	CRES 303 FREE MACHINING	
	10281	PLATING SILVER,FASTENERS ONLY	
SL6082AX	10003	AL 2024-T851/T6/T62 BR RD & WR	
	10276	COATING ANODIC TYPE 1	
	10315	CRES 302/304/316 FASTENER ONLY	

MSFC-HDBK-527 REV F 9999942 0007176 4

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
SL6082AX	10281	PLATING SILVER,FASTENERS ONLY	
SL6082AX-X	10003	AL 2024-T851/T6/T62 BR RD & WR	
	10325	AL 6061 ANN SHT & PLT	
	10276	COATING ANODIC TYPE 1	
	10315	CRES 302/304/316 FASTENER ONLY	
	00666	CTNG CONVERSION CHROMATE INORG	
	10281	PLATING SILVER,FASTENERS ONLY	
SL6101CX-XXS	10351	CRES 304 ANN BAR SHP FRG WIRE	
	10281	PLATING SILVER,FASTENERS ONLY	
SL6103A	10292	AL 2024-T6 BAR ROD & WIRE	
	10276	COATING ANODIC TYPE 1	
SL6104A	10292	AL 2024-T6 BAR ROD & WIRE	
	10276	COATING ANODIC TYPE 1	
SL6104C	10315	CRES 302/304/316 FASTENER ONLY	
SL6104CX-XXXS	10315	CRES 302/304/316 FASTENER ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
SL6106CXXS	10325	AL 6061 ANN SHT & PLT	
	10315	CRES 302/304/316, FASTENER ONLY	
	00666	CTNG CONVERSION CHROMATE INORG	
	10281	PLATING SILVER,FASTENERS ONLY	
SL6107CXXS	10281	PLATING SILVER,FASTENERS ONLY	
	10314	STEEL INVAR 36 BAR	
SL850CXXM	30121	CRES 17-7PH/17-4PH COND A	
	05302	LUBE DRY DAG NO 206 MOS2 INORG	
SL854CXXXS	10089	CRES 302 COND B BAR AND WIRE	
	10281	PLATING SILVER,FASTENERS ONLY	
SLP 2110	10469	CU WIRE /SILVER PLATED	WIRE CONDUCTOR
	01342	KAPTON INSUL	
SLR4001	10400	NI INCO X750 STA SHT STP PLT	
SLR4001SPI	10400	NI INCO X750 STA SHT STP PLT	
	10281	PLATING SILVER,FASTENERS ONLY	
SMGXXA	10023	AL 6061-T6/651 RLD BAR SHP ROD	
	10277	COATING ANODIC TYPE 2	
SMR 1205	10124	CRES A286	NUT
	10039	SILVER PLATED	
SMR 2205	10124	CRES A286	NUT
	10039	SILVER PLATED	
SMR 3205	10124	CRES A286	NUT , ANCHOR
	10039	SILVER PLATED	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
SMR 4205	10124	CRES A286	NUT
	10039	SILVER PLATING	
SMR 5205	10124	CRES A286	NUT
	10039	SILVER PLATING	
SMXXA	10023	AL 6061-T6/651 RLD BAR SHP ROD	
	10277	COATING ANODIC TYPE 2	
SP 750.0080	10430	CRES 17-4PH	TUBE-FITTING
SPL192L-SU-11	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
SPL96-12NL	00597	LUBE DRY	
	30082	PLATING CADMIUM & CHROMATE	
	30092	STEEL H-11 BAR & FORGING	
SPS 61170	10124	CRES A286	NUT , SELF-LOCKING
	10039	PLATING SILVER	
SR-6N-6-N	10046	PLATING NI ELECTROLESS	
	10232	SPRING STEEL MUSIC WIRE	
SRXXX	10416	CRES 17-4PH H1150 BAR ROD FORG	
	05723	LUBE DRY	
SRXXX-0024	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
SRXXX-0025	10267	CRES A286 FASTENER MATL ONLY	
	05520	LUBE DRY TIO LUBE 460 MS21063	
SS-51051K5900	10358	STEEL SAE/AISI 1008-1010	
SSBL60N-018-03	30080	CRES 303 FREE MACHINING	
	30002	CRES 440A,440B,440C BAR	
	00019	NYLON PLASTIC	
	10147	SPRING 17-7PH CH 900 WIRE STP	
SSR-0237	10350	CRES 301/302 ANN SHT STDS ONLY	
ST 11[illegible]	10124	CRES A286	WASHER
ST 20141	10267	CRES A286	INSERT
ST 20345	05142	RUBBER SILICONE	O-RING
ST 20431	10267	CRES A286	SCREW
ST 20432	10268	CRES 300 SERIES	SCREW
ST 20433	10271	BE-CU	JACK
ST 20441	30069	KOVAR (MICROCICUITS)	VOLT FREQUENCY CONVERT

MSFC-HDBK-527 REV F 9999942 0007178 8

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
ST 20442	05467	RUBBER CONSIL 861	GASKET
ST-20473-XX	10205	AL 2024-T851	SLEEVE
	00666	CTNG CONVERSION CHROMATE	
ST-20474-XX	10205	AL 2024-T851	UNION,FLARE TUBE
	00666	CTNG CONVERSION CHROMATE	
ST-20481-12	30111	AL 2024-T4	CLAMP
	00666	CTNG CONVERSION CHROMATE	
	00016	TEFLON TFE	
ST20475	10087	CRES 301	STRAP,RETAINING
	10262	CRES 302	
	10456	CRES A286	
ST2850005ME0002	10507	AL 6061/6262-0/T6/T9 BR	
	10277	COATING ANODIC TYPE 2	
	10089	CRES 302 COND B BAR AND WIRE	
	30080	CRES 303 FREE MACHINING	
	10318	CRES 304L/316L WIRE/SCRN/CLOTH	
	10095	CRES 316 ANN SHT PLT STRIP	
	30002	CRES 440A,440B,440C BAR	
	00515	GREASE PERFLUORINATED	
	05084	KEL-F UNPLASTICIZED	
	05005	RUBBER VITON FLUID RESISTANT	
	10147	SPRING 17-7PH CH 900 WIRE STP	
	10419	SPRING TEMPER CRES 302 WIRE	
	00016	TEFLON TFE	
ST2850006ME0002	10507	AL 6061/6262-0/T6/T9 BR	
	10277	COATING ANODIC TYPE 2	
	10089	CRES 302 COND B BAR AND WIRE	
	30080	CRES 303 FREE MACHINING	
	10318	CRES 304L/316L WIRE/SCRN/CLOTH	
	10095	CRES 316 ANN SHT PLT STRIP	
	30002	CRES 440A,440B,440C BAR	
	00515	GREASE PERFLUORINATED	
	05084	KEL-F UNPLASTICIZED	
	05005	RUBBER VITON FLUID RESISTANT	
	10147	SPRING 17-7PH CH 900 WIRE STP	
	10419	SPRING TEMPER CRES 302 WIRE	
	00016	TEFLON TFE	
ST2850006ME0003	10507	AL 6061/6262-0/T6/T9 BR	
	10277	COATING ANODIC TYPE 2	
	30002	CRES 440A,440B,440C BAR	
	10419	SPRING TEMPER CRES 302 WIRE	
	00016	TEFLON TFE	
ST4760023ME0009	20900	40MXXXXX CONNECTOR	
	10022	AL 6061-T6/62/651 SHT & PLT	
	10485	AL A356-T51	
	10046	PLATING NI ELECTROLESS	
	05257	POTTG CPD STYCAST 2850FT/9 EPO	

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
STSV 057	10267	CRES A286	PIN
STSV 060	10431 05495	CRES 300 SERIES RULON J	BEARING , SLEEVE
STSV 061	10090 30119	CRES 304 CTING ANODIZE	WASHER FLAT
STSV 065	05495	RULON J	WASHER
STSV 067	10218 02997 30119	AL 6061 CLAMP CUSHION SILICONE GLASS CTING ANODIZE	CLAMP
STSV 089	00367	TUBING KYNAR HST	TUBING SHRINKABLE
STSV 110	10088 00649	CRES 301 TEFLON	CLAMP
STSV 153	10222 20108	MONEL SILICONE RUBBER	GASKET,CONNECTOR
STSV 176	10083	CRES 316 L	TEE WELDED
STSV 194	10268	CRES 300 SERIES	WASHER
STSV 233	10366	AL 1100	PLATE I.D.
STSV 242	10366	AL 1100	LABEL
STSV 243	10090 10336	CRES 304 CRES 305	RECEPTACLE
STSV 244	10423	CRES 302	TURNLOCK FASTENER
STSV 247	10366	AL 1100	LABEL
STSV 248	10366	AL 1100	LABEL
STSV 249	10366	AL 1100	LABEL
STSV 259	05005	RUBBER VITON	TUBE
STSV 416	50211	AL 5652	PLATE I.D.
STSV061AB171	50092	AL 2024	WASHER
STSV101	10475	CRES 305	RIVET ,SEMI-TUBULAR
STSV191	10392	CRES A286/304	SCREW ,CAPTIVE
STSV252	05098 10431	CLAMP CUSH SILICONE/GLASS CRES 300 SERIES	CLAMP LOOP CUSHIONED
STSV461-10	10294	CRES 302	INSERT , HELICOIL

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
STSV463A03-6	10069	TI 6AL 4V	SCREW
SV777271-1	10069	TI 6AL 4V	SCREW
SW 2600	10315	CRES 302	WASHER
SW 4650	30080	CRES 303	WASHER
SWT-X/X	00016	TEFLON TFE	
T0 XX	30044	BED	COOL WASHER
T018-180-140	10391	CRES 302/304/316 SHT PLT WIRE	
T020	10391	CRES 302/304/316 SHT PLT WIRE	
TA09C89SSRXXHB	02997 10250	CLAMP CUSHION/SILICONE/GLASS MAGNETIC STL NI-FE ANN FRG	
TA552TD05T	30111 00016	AL 2024-T3/T4 SHEET TEFLON TFE	
TA555THX	10097	CRES 321 ANN SHT PLT STRIP	
TA558TSS4T	10294 00016	CRES 302 ANN THRU 1/2 HD PT SH TEFLON TFE	
TA562TSS2-5T	10294 00016	CRES 302 ANN THRU 1/2 HD PT SH TEFLON TFE	
TA564WSSXXT	10294 10097 00016	CRES 302 ANN THRU 1/2 HD PT SH CRES 321 ANN SHT PLT STRIP TEFLON TFE	
TA713WSSXXT	10294 10097 00016	CRES 302 ANN THRU 1/2 HD PT SH CRES 321 ANN SHT PLT STRIP TEFLON TFE	
TA715HX	10097	CRES 321 ANN SHT PLT STRIP	
TA716WSSXXT	10294 10097 00016	CRES 302 ANN THRU 1/2 HD PT SH CRES 321 ANN SHT PLT STRIP TEFLON TFE	
TA721SS	10294 10097	CRES 302 ANN THRU 1/2 HD PT SH CRES 321 ANN SHT PLT STRIP	
TA724SSXXT	10294 10097 00016	CRES 302 ANN THRU 1/2 HD PT SH CRES 321 ANN SHT PLT STRIP TEFLON TFE	
TA779THXX	10097 00016	CRES 321 ANN SHT PLT STRIP TEFLON TFE	
TA829SSX	10294 10097	CRES 302 ANN THRU 1/2 HD PT SH CRES 321 ANN SHT PLT STRIP	

MSFC-HDBK-527 REV F 9999942 0007181 8

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
TA9C89DXXT	10408	AL 2024T3/T4X/T6X/T8XX CLD SHT	
	00016	TEFLON TFE	
TC 105	10282	AL 3003	MOUNTING PLATE
TC-142	00019	NYLON PLASTIC	MOUNTING BASE
TC-815	00019	NYLON PLASTIC	MOUNTING BASE
TCZ 223	05205	TEFZEL ETFE	BUNDLE MARKER
TEILE NR. XXX	05005	RUBBER VITON	O-RING
TL 212	10098	CRES 321	CLAMP
TLN1020CPD2-X	10267	CRES A286 FASTENER MATL ONLY	NUT,SELF-ALIGN
	05723	LUBE DRY	
TLN1023CD3-XX	10267	CRES A286 FASTENER MATL ONLY	NUT,SELF-ALIGN
	00597	LUBE DRY	
TLN1024PPD3-XX	10384	INCONEL 718	NUT,SELF-ALIGN
	00597	LUBE DRY	
TNC-PL2-M-30	10271	BE-CU HT/AT BAR ROD WIRE FRG	
	10321	BRASS, ALL FORM	
	10431	CRES 300 SERIES NON-FREE MACH	
	10294	CRES 302 ANN THRU 1/2 HD PT SH	
	10090	CRES 304 ANN SHT PLT STRIP	
	10311	PLATING COPPER ELECTRO DEPOSIT	
	10328	PLATING GOLD	
	05735	RUBBER SM3500-41 SILICONE	
	00016	TEFLON TFE	
TO 18	05369	MOLD CPD (DAP)	MOUNTING PAD
TO 5	05369	DAP	MOUNTING PAD
TO 63	05803	MOLD CPD DAP/CARBON PROPRIETOR	SHOULDER WASHER
TR24195	10391	CRES 302/304/316 SHT PLT WIRE	
	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	
TX-0506-X G	10321	BRASS ALL FORMS	THEMA-LINK RETAIN
	30169	BRASS BRONZE	
TXP 0508 B	50061	AU PLATING	RETAINING LINK
	10716	BE-CU	
	10321	BRASS	
TY-XXM	10350	CRES 301/302 ANN SHT STDS ONLY	CABLE TIE
	05253	NYLON PLASTIC	
TYS5/TYS-15	10350	CRES 301/302 ANN SHT STDS ONLY	

MSFC-HDBK-527 REV F 9999942 0007182 T

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
TYZ 25M	05205	TEFZEL (ETFE)	TIE WRAP
TYZ 28M	05205	TEFZEL (ETFE)	TIE-WRAP
TYZ 51 M	05205	TEFZEL	BUNDLE MARKER
TYZ-XXM	05205	TEFZEL ETFE	STRAP TIEDOWN
UN 2753 (SL-MA001)	99001	MATERIALS UNIDENTIFIABLE	CONNECTOR
UNC 4-40	10321	BRASS	NUT
UXS	99010	NOT TO BE USED ON SHUTTLE	
V01600	10046 10513	PLATING NI ELECTROLESS STEEL 4XXX/8XXX OVER 220 KSI	
VD-114	10087	CRES 301	SPRING
VD-117 J	10087	CRES 301	SPRING
VD-143A	10087	CRES 301	SPRING
VD-180K	10087	CRES 301	SPRING
VD-186	10087	CRES 301	SPRING
VD261-0306	30080 10308	CRES 303 FREE MACHINING PLATING NICKEL ELECTRODEPOSIT	
VN324BCXXX	10267 50124	CRES A286 FASTENER MATL ONLY PLATING CADMIUM	NUT,SELF-LOCKING
VN324DXXX	10267 20247	CRES A286 FASTENER MATL ONLY LUBE DRY ON METALLIC FASTENER	NUT,SELF-LOCKING
VN324NPXXX	10267	CRES A286 FASTENER MATL ONLY	NUT,SELF-LOCKING
VN405NPXXX	10267	CRES A286 FASTENER MATL ONLY	NUT,SELF-LOCKING
VN465AXXX	00597 50124 30096	LUBE DRY PLATING CADMIUM STEEL 8740 BAR FORGING RING	NUT,TWELVE POINT
VN900-XXX	10124	CRES A286 140 KSI SHEET & PLT	WASHER
VO-1400	10046 10513	PLATING NI ELECTROLESS STEEL 4XXX/8XXX OVER 220 KSI	
VO-3200	10046 10513	PLATING NI ELECTROLESS STEEL 4XXX/8XXX OVER 220 KSI	
VP10WRX	10308 10515 10359	PLATING NICKEL ELECTRODEPOSIT STEEL 1055-1090 LOW CARBON STEEL AISI/SAE 1010 TO 1040	

MSFC-HDBK-527 REV F 9999942 0007183 1

Information Handling Services, 2000

DOCUMENT NUMBER	MATCD	MANUFACTURERS DESIGNATION	NOMENCLATURE
VS2587-XX-XX	10267	CRES A286 FASTENER MATL ONLY	BOLT,TWELVE PNT
VS2768-XX-XX	10267	CRES A286 FASTENER MATL ONLY	BOLT,TWELVE PNT
VSF1015N	10225	NI 200/201	SEAL
VSF1015NXX	10225	NI 200/201 ANN (ALL FORMS)	
W0492-007-S	10294	CRES 302 ANN THRU 1/2 HD PT SH	
WFL1-G150-16BB	10431	CRES 300 SERIES NON-FREE MACH	
	10091	CRES 304 COND B BAR SHP FRG WI	
	05204	RUBBER NITRILE (NRB)	
X-5XXCH	10370	CRES 316 COND A & B BAR	
	05617	GLASS TEMPERED (INORGANIC)	
	00016	TEFLON TFE	
X563	10308	PLATING NICKEL ELECTRODEPOSIT	
	10358	STEEL SAE/AISI 1008-1010	
XE-18100	10321	BRASS, ALL FORM	
	10308	PLATING NICKEL ELECTRODEPOSIT	
XX-18201	10321	BRASS, ALL FORM	
	10322	BRONZE PHOSPHOR, ALL FORMS	
	10308	PLATING NICKEL ELECTRODEPOSIT	
Z1200J	10100	CRES 347 ANN BAR SHP FRG WIRE	
	10281	PLATING SILVER,FASTENERS ONLY	
Z1855	10267	CRES A286 FASTENER MATL ONLY	
	10281	PLATING SILVER,FASTENERS ONLY	

Information Handling Services, 2000

TABLE 4

FOREIGN ALLOY CROSS REFERENCE

Information Handling Services, 2000

TABLE 4A

ALUMINUM

Information Handling Services, 2000

DATE: 12/23/88
ALUMINUM

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
1	ENGLAND	1099
108	US	208.0
11S	US	2011
122	US	222.0
123	ALCAN	443.0
125	ALCAN	355.0
127	ALCAN	....
13	US	413.0
135	ALCAN	356.0
138	US	238.0
142	US	242.0
143	ALCAN	A380.0
14S	US	2014
150A	ENGLAND	2017
160N	ALCAN	A413.0
160X	ALCAN	A413.0
162	ALCAN	A332.0
164	ALCAN	384.0
16S	ALCAN	2117
17S	ALCAN	2017
17S	US	2017
18S	ALCAN	2018
18S	US	2018
19S	US	295.0
19S	ALCAN	2218
1A	ENGLAND	1080
1B	ENGLAND	1050
1C	ENGLAND	1200
1E	ENGLAND	1350
1S	ALCAN	1050
20	SAE	3004
201	SAE	5052
202	SAE	2011
203	SAE	2218
204	SAE	2117
205	SAE	4043
207	SAE	5050
208	SAE	5154
209	SAE	5357
210	SAE	6003
211	SAE	6062
212	SAE	6063
213	SAE	6951
214	SAE	7072
214	US	514.0
215	SAE	7075
218	ALCAN	242.0
218	US	518.0
220	US	520.0
224	ALCAN	B295.0
225	ALCAN	295.0
236	ALCAN	....
238.0	ASTM	238.0
24	SAE	2024
240	SAE	2024
241	SAE	7075
242	ALCAN	....
242	SAE	3004
244	SAE	6061
245	SAE	3003
246	SAE	2014
246B	ENGLAND	2618
247	SAE	#11 BRAZING
248	SAE	#12 BRAZING
249	SAE	#21 BRAZING
24S	ALCAN	2024
24S	US	2024
25	SAE	1100
250	ALCAN	222.0
250	SAE	#22 BRAZING
251	SAE	5454
252	SAE	5457
253	SAE	6463
25S	ALCAN	2025
25S	US	2025
26	SAE	2017
260	SAE	2014
26S	ALCAN	2014
270	SAE	2018
280	SAE	6151
281	SAE	6061
28S	ALCAN	2011
29	SAE	3003
290	SAE	4032
2S	ALCAN	1200
2S	US	1100
3.0185	GERMANY	8079
3.0205	GERMANY	1200
3.0255	GERMANY	1100
3.0257	GERMANY	1350
3.0270	GERMANY	1070
3.0275	GERMANY	1070A
3.0280	GERMANY	1080
3.0284	GERMANY	1090
3.0285	GERMANY	1080A
3.0305	GERMANY	1090
3.0385	GERMANY	1199
3.0505	GERMANY	3105
3.0515	GERMANY	3103
3.0517	GERMANY	3003
3.0525	GERMANY	3005
3.0526	GERMANY	3004
3.0615	GERMANY	6262
3.0805	GERMANY	....
3.1124	GERMANY	2117
3.1254	GERMANY	2014
3.1255	GERMANY	2014
3.1305	GERMANY	2117
3.1324	GERMANY	2024
3.1325	GERMANY	2017

Information Handling Services, 2000

DATE: 12/23/88
ALUMINUM

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
3.1335	GERMANY	2017 (CLAD)
3.1354	GERMANY	2024
3.1355	GERMANY	2024
3.1364	GERMANY	2024 (CLAD)
3.1365	GERMANY	2024
3.1645	GERMANY	2017
3.1655	GERMANY	2011
3.1734	GERMANY	A242.0
3.1854	GERMANY	B295.0
3.1924	GERMANY	2418
3.2134	GERMANY	355.0
3.2245	GERMANY	4043
3.2285	GERMANY	4047
3.2305	GERMANY	6101
3.2315	GERMANY	6351
3.2316	GERMANY	....
3.2318	GERMANY	6351
3.2345	GERMANY	4043
3.2364	GERMANY	356.0
3.2374	GERMANY	A356.0
3.2378	GERMANY	6061
3.2581	GERMANY	413.0
3.2582	GERMANY	413.0
3.2583	GERMANY	413.0
3.2584	GERMANY	413.0
3.3200	GERMANY	6063
3.3206	GERMANY	6060
3.3207	GERMANY	6101
3.3208	GERMANY	....
3.3214	GERMANY	6061
3.3308	GERMANY	1095
3.3309	GERMANY	5007
3.3315	GERMANY	5005
3.3318	GERMANY	1095
3.3319	GERMANY	5008
3.3325	GERMANY	5051
3.3328	GERMANY	1095
3.3329	GERMANY	....
3.3334	GERMANY	5052
3.3354	GERMANY	5056
3.3515	GERMANY	5005
3.3523	GERMANY	5052
3.3524	GERMANY	5052
3.3525	GERMANY	5251
3.3527	GERMANY	....
3.3535	GERMANY	5754
3.3536	GERMANY	5754
3.3537	GERMANY	5454
3.3547	GERMANY	5083
3.3548	GERMANY	5183
3.3555	GERMANY	5056
3.3575	GERMANY	5556
3.3591	GERMANY	520.0
3.4335	GERMANY	7005
3.4338	GERMANY	7104
3.4344	GERMANY	7079
3.4345	GERMANY	7079
3.4354	GERMANY	7009
3.4355	GERMANY	7004
3.4364	GERMANY	7075
3.4365	GERMANY	7075
3.4374	GERMANY	7075 (CLAD)
3.4375	GERMANY	7075 (CLAD)
3.4415	GERMANY	7072
300	SAE	....
303	SAE	A384.0
304	SAE	C443.0
305	SAE	A413.0
306	SAE	380.0
306	SAE	A380.0
308	SAE	380.0
308	SAE	A380.0
309	SAE	A360.0
310	SAE	D712.0
311	SAE	705.0
312	SAE	707.0
313	SAE	A712.0
314	SAE	C712.0
315	SAE	713.0
319	US	319.0
320	ALCAN	514.0
320	SAE	514.0
321	ALCAN	B514.0
321	SAE	A332.0
322	ALCAN	A514.0
322	SAE	355.0
323	SAE	356.0
324	SAE	520.0
324	US	324.0
324A	ENGLAND	4032
326	SAE	319.0
327	SAE	328.0
328	SAE	....
329	SAE	....
32S	US	4032
33	SAE	213.0
332	SAE	F332.0
333	US	333.0
334	SAE	....
335	SAE	C355.0
336	SAE	A356.0
33S	ALCAN	4043
34	SAE	222.0
340	ALCAN	518.0
346A	ENGLAND	6351
34S	ALCAN	4343
35	SAE	443.0
350	ALCAN	520.0
354	US	354.0
355	US	355.0

Information Handling Services, 2000

DATE: 12/23/88
ALUMINUM

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
356	US	356.0
3567	ITALY	1200
3568	ITALY	3003
3568	ITALY	3103
3569	ITALY	6063
357	US	357.0
3570	ITALY	6101
3571	ITALY	6082
3571	ITALY	6351
3572	ITALY	4032
3573	ITALY	5050
3574	ITALY	5052
3575	ITALY	5039
3576	ITALY	5056
3577	ITALY	2117
3578	ITALY	2018
3579	ITALY	2017
3580	ITALY	2017
3581	ITALY	2014
3582	ITALY	2014
3583	ITALY	2024
3584	ITALY	2024
359	US	359.0
3599	ITALY	356
35S	ALCAN	4047
360	US	360.0
364	US	364.0
372B	ENGLAND	6063
3735	ITALY	7075
3736	ITALY	7080
3737	ITALY	7001
3738	ITALY	7001
38	SAE	295.0
380	SAE	....
380	US	380.0
384	US	384.0
384	US	A384.0
38S	ALCAN	4032
39	SAE	242.0
39	SAE	A242.0
390	US	390.0
392	US	392.0
3S	ALCAN	3003
3S	US	3003
40E	US	D712.0
42S	ALCAN	2618
43	US	443.0
43	US	A443.0
43	US	B443.0
432	ALCAN	A712.0
43S	US	4043
44S	US	4343
4507	ITALY	1050
4508	ITALY	1070
4509	ITALY	1080

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
450A	ENGLAND	6066
4510	ITALY	5005
45S	US	4045
460A	ENGLAND	6066
47S	US	4047
4S	ALCAN	3004
4S	US	3004
5010	ENGLAND	2014
5014	ENGLAND	2218
5020	ENGLAND	2014
5024	ENGLAND	7076
5030	ENGLAND	2014
5034	ENGLAND	7079
5040	ENGLAND	2014
5044	ENGLAND	7076
5050	ENGLAND	7080
5054	ENGLAND	7079
5060	ENGLAND	7080
5064	ENGLAND	7080
5070	ENGLAND	....
5074	ENGLAND	7001
5080	ENGLAND	6351
5084	ENGLAND	....
5090	ENGLAND	2024
5094	ENGLAND	7076
50S	ALCAN	6063
50S	US	5050
5100	ENGLAND	2024
52S	US	5052
53S	US	6053
54S	ALCAN	5039
55S	ALCAN	6053
56S	ALCAN	5056
56S	US	5056
57S	ALCAN	5052
603	US	705.0
607	US	707.0
613	US	713.0
6154	ALCAN	EC
6170	ITALY	6061
61S	ALCAN	6151
61S	US	6061
6211	ALCAN	5456
6223	ALCAN	5356
6225	ALCAN	3005
6227	ALCAN	7178
62S	ALCAN	6066
62S	US	6062
6348	ALCAN	D712.0
63S	US	6063
64S	US	X6064
65S	ALCAN	6061
66S	US	6066
687B	ENGLAND	7080
710B	ENGLAND	2014

Information Handling Services, 2000

DATE: 12/23/88
ALUMINUM

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
717	ENGLAND	2218
724	ENGLAND	2218
72S	ALCAN	7072
72S	US	7072
730	ALCAN	A850.0
731A	ENGLAND	2218
745	ENGLAND	2218
746C	ENGLAND	2014
74S	ALCAN	7004
750	US	850.0
75S	ALCAN	7075
75S	US	7075
76S	US	7076
79S	ALCAN	7079
79S	US	7079
91E	ENGLAND	6101
99.3	US	1230
99.35	US	1235
99.60	ALCAN	1060
99.70	ALCAN	1070
99.75	ALCAN	1075
99.75	US	1175
99.8	US	1180
99.30	ALCAN	1080
99.35	ALCAN	1085
99.85	US	1285
99.90	ALCAN	1090
99.950	ALCAN	1095
99.99	ALCAN	1199
990	CANADA	1200
990A	ASTM	1100
990C	CANADA	1100
995	CANADA	1050
9950	CANADA	1050
996A	ASTM	1060
9970	CANADA	1070
9975	CANADA	1075
9980	CANADA	1080
9985	CANADA	1085
9990	CANADA	1090
9995	CANADA	1095
9999	CANADA	1099
A-G1	FRANCE	5050
A-G1.5	FRANCE	5050
A-G10	FRANCE	520.0
A-G11	FRANCE	520.0
A-G2	FRANCE	5051
A-G2.5	FRANCE	5052
A-G2M	FRANCE	5251
A-G3	FRANCE	X5754
A-G4	FRANCE	5082
A-G4MC	FRANCE	5086
A-G5	FRANCE	5556
A-G5MC	FRANCE	5907
A-G7	FRANCE	5556

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
A-G0.6	FRANCE	5005
A-GS	FRANCE	6063
A-GS/L	FRANCE	6101
A-M	FRANCE	3003
A-M1	FRANCE	3003
A-M1G	FRANCE	3004
A-MG05	FRANCE	3004
A-SG	FRANCE	6181
A-SGM	FRANCE	6351
A-SGM0.3	FRANCE	6081
A-SGM0.7	FRANCE	6082
A-U10G	FRANCE	222.0
A-U10S4	FRANCE	238.0
A-U2G	FRANCE	2117
A-U2GN	FRANCE	2618
A-U2GNS	FRANCE	2618
A-U2N	FRANCE	2618
A-U4G	FRANCE	2017
A-U4G1	FRANCE	2024
A-U4N	FRANCE	2218
A-U4NT	FRANCE	242.0
A-U4PB	FRANCE	2011
A-U4SG	FRANCE	2014
A-Z3G2	FRANCE	7004
A-Z4G	FRANCE	7004
A-Z5GU	FRANCE	7075
A-Z6G	FRANCE	7005
A-Z8GU	FRANCE	7049
A1-12SI	SWISS	413.0
A1-12SI	SWISS	A413.0
A108	US	308.0
A13	US	A413.0
A132	US	A332.0
A140	US	A240.0
A142	US	A242.0
A143	ALCAN	....
A17S	US	2117
A199.5	GERMANY	EC
A1MGSI	GERMANY	6101
A214	US	A514.0
A218	US	A535.0
A2S	US	1200
A320	ALCAN	F514.0
A344	US	A444.0
A356	US	A356.0
A357	US	A357.0
A360	US	A360.0
A380	US	A380.0
A4	FRANCE	1200
A43	US	C443.0
A45	FRANCE	1100
A5	FRANCE	1050
A5/L	FRANCE	EC
A50S	US	5005
A51S	US	6151

Information Handling Services, 2000

DATE: 12/23/88
ALUMINUM

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
A54S	US	5154
A56S	ALCAN	5556
A612	US	A712.0
A7	FRANCE	1070
A7-G3	FRANCE	5657
A750	US	A850.0
A8	FRANCE	1080
A9	FRANCE	1099
AA1S	US	1095
AB1S	US	1085
AC1S	US	1070
AD1S	US	1050
AE1S	US	1030
AG-G3	FRANCE	....
AL99	GERMANY	1200
AL99.5	GERMANY	1050
AL99.7	GERMANY	1070
AL99.8	GERMANY	1080
AL99.9	GERMANY	1090
AL99.98R	GERMANY	1199
ALCU10FEMG	ITALY	222.0
ALCU2.5MGSI	ITALY	2117
ALCU3.5FEMGNI	ITALY	2018
ALCU4.4SIMNMG	ITALY	2014
ALCU4.5	ITALY	295.0
ALCU4.5MGMN	ITALY	2024
ALCU4.5MGMN-PLACC	ITALY	2024
ALCU4MGMN	ITALY	2017
ALCU4MGMN-PLACC	ITALY	2017
ALCU4NIMG	ITALY	242.0
ALCU4NIZMG2	ISO	242.0
ALCU4SI	ISO	295.0
ALCUFONT 10	ITALY	222.0
ALCUFONT 12	ITALY	222.0
ALCUFONT 4.5	ITALY	295.0
ALCUFONT 8	ITALY	....
ALCUMG0.5	GERMANY	2117
ALCUMG1	GERMANY	2017
ALCUMG1PL	GERMANY	2017
ALCUMG2	GERMANY	2024
ALCUMG2PL	GERMANY	2024
ALCUMGPB	GERMANY	2011
ALCUSIMN	GERMANY	2014
ALLCAST	US	319.0
ALLIAGE Y	FRANCE	242.0
ALMAG35	US	535.0
ALMG0.9	ITALY	5005
ALMG1	GERMANY	5005
ALMG1.5	ITALY	5050
ALMG10	GERMANY	520.0
ALMG10	ISO	520.0
ALMG10	ITALY	520.0
ALMG2.5	ITALY	5052
ALMG3	ISO	514.0
ALMG3.5	ITALY	5039

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
ALMG3SI	ISO	514.0
ALMG5	GERMANY	5056
ALMG5	GERMANY	5083
ALMG5	ITALY	5056
ALMG7	GERMANY	5556
ALMG7	ITALY	518.0
ALMG9SI	ISO	518.0
ALMGMN	GERMANY	3004
ALMGSI0.5	GERMANY	6063
ALMGSI1	GERMANY	6351
ALMN	GERMANY	3003
ALMN1.2	ITALY	3003
ALP99.0	ITALY	1200
ALP99.5	ITALY	1050
ALP99.7	ITALY	1070
ALP99.8	ITALY	1080
ALPAX	ENGLAND	A413.0
ALSI0.4MG	ITALY	6063
ALSI0.5MG	ITALY	6101
ALSI12	GERMANY	4047
ALSI12	GERMANY	A413.0
ALSI12	ISO	413.0
ALSI12	ISO	A413.0
ALSI12MGCUNI	ITALY	4032
ALSI13	ITALY	413.0
ALSI13	ITALY	A413.0
ALSI1MGMN	ITALY	6351
ALSI5	GERMANY	4043
ALSI5CU1	GERMANY	355.0
ALSI5CUMG	ITALY	355.0
ALSI6CU4	ISO	319.0
ALSI7MG	ISO	356.0
ALSI7MGMN	ITALY	356.0
ALSI8.5CU	ITALY	380.0
ALSI8.5CU	ITALY	A380.0
ALSIFONT S5C	ITALY	....
ALSIFONT S9CF	ITALY	A380.0
ALUMINAL C10	ENGLAND	520.0
ALUMINAL C12	ENGLAND	222.0
ALUMINAL C13	ENGLAND	A332.0
ALUMINAL C15	ENGLAND	242.0
ALUMINAL C2	ENGLAND	....
ALUMINAL C6	ENGLAND	A413.0
ALZN5.8MGCU	ITALY	7080
ALZN5.8MGCU-PLACC	ITALY	7080
ALZN5MG	ISO	D712.0
ALZN7.8GCU	ITALY	7001
ALZN7.8MGCU-PLACC	ITALY	7001
ALZNMG1	GERMANY	7005
ALZNMG3	GERMANY	7004
ALZNMGCU0.5	GERMANY	7079
ALZNMGCU1.5	GERMANY	7075
ALZNMGCU1.5PL	GERMANY	7075
AS10	ITALY	....
AS12N2G	FRANCE	A332.0

DATE: 12/23/88
ALUMINUM

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
AS12UN	FRANCE	4032
AS13	FRANCE	413.0
AS13	FRANCE	A413.0
AS5	ITALY	C355.0
B125	ALCAN	C355.0
B135	ALCAN	A356.0
B143	ALCAN	F332.0
B150	ALCAN	360.0
B160	ALCAN	413.0
B18S	US	2218
B195	US	B295.0
B214	US	B514.0
B218	US	B535.0
B25S	US	2225
B26S	ALCAN	2014
B33S	ALCAN	4543
B4S	ALCAN	3004
B51S	ALCAN	6351
B53S	ALCAN	5454
B53S	US	6253
B54S	ALCAN	5082
B54S	US	5254
B57S	ALCAN	5005
B730	ALCAN	B850.0
B750	US	B850.0
B75S	ALCAN	7079
B77S	US	7277
BA1S	US	1099
BB1S	US	1188
BC1S	US	1080
BD1S	US	1060
BE1S	US	1145
C113	US	213.0
C125	ALCAN	355.0
C135	ALCAN	357.0
C143	ALCAN	380.0
C1S	ALCAN	EC
C355	US	C355.0
C35S	ALCAN	4145
C4	CANADA	295.0
C43S	US	4343
C4A	ASTM	295.0
C50S	ALCAN	6463
C51S	ALCAN	6005
C53S	ALCAN	5554
C54S	ALCAN	5154
C57S	ALCAN	5252
C57S	US	5357
C612	US	C712.0
C65S	ALCAN	6061
C74S	ALCAN	7104
C75S	ALCAN	7076
C77S	ALCAN	7001
CB1S	US	1185
CB60	CANADA	2011

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
CB60A	ASTM	2011
CC1S	US	1180
CENTRAL A	FRANCE	A332.0
CENTRALIT	FRANCE	222.0
CENTRASIL	FRANCE	A332.0
CEÑALUM C	ENGLAND	242.0
CG100	CANADA	222.0
CG100A	ASTM	222.0
CG30	CANADA	2117
CG30A	ASTM	2117
CG42	CANADA	2024
CG42A	ASTM	2024
CM41	CANADA	2017
CM41A	ASTM	2017
CN42	CANADA	2018
CN42	CANADA	242.0
CN42A	ASTM	242.0
CN42C	ASTM	2018
CN42D	ASTM	2218
CORROFONT M10	ITALY	520.0
CQ51A	ASTM	201.0
CS104A	ASTM	238.0
CS41A	ASTM	2014
CS41C	ASTM	2025
CS41N	CANADA	2014
CS41P	CANADA	2025
CS43A	ASTM	208.0
CS66A	ASTM	....
CS74A	ASTM	....
D12	ENGLAND	....
D1S	ALCAN	EC
D2S	ALCAN	1100
D2S	ALCAN	1130
D3S	ALCAN	3003
D4S	ALCAN	3004
D50S	ALCAN	6101
D54S	ALCAN	5083
D612	US	D712.0
D74S	ALCAN	7005
DB1S	US	1285
DD1S	US	1260
DE1S	US	1330
DG6	SWISS	356.0
DHP1007	ENGLAND	2124 T851PLATE
DHP1008	ENGLAND	2024 T8511EXT
DHP1028	ENGLAND	7475 T73PLATE
DHP1029	ENGLAND	2028 T851TUBE
DHP1045	ENGLAND	2024 T81SHEET
E1S	ALCAN	1145
E50S	ALCAN	6363
E54S	ALCAN	5086
EC	US	EC
EC124	GERMANY	A332.0
F132	US	F332.0
F18S	US	2618

Information Handling Services, 2000

DATE: 12/23/88
ALUMINUM

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
F214	US	F514.0
F52S	US	5652
FB1S	US	1090
FC1S	US	1170
G10	CANADA	520.0
G10A	ASTM	520.0
G1A	ASTM	5050
G1B	ASTM	5005
G4	CANADA	514.0
G4A	ASTM	514.0
G57S	ALCAN	5457
G8	CANADA	518.0
G8A	ASTM	518.0
GM31A	ASTM	5454
GM31N	CANADA	5454
GM40	CANADA	5082
GM40A	ASTM	5086
GM41	CANADA	5083
GM41A	ASTM	5083
GM50A	ASTM	5056
GM50N	CANADA	5556
GM50R	CANADA	5056
GM51A	ASTM	5456
GM70B	ASTM	535.0
GR20	CANADA	5052
GR20A	ASTM	5052
GR20B	ASTM	5652
GR40	CANADA	5154
GR40A	ASTM	5154
GR40B	ASTM	5254
GS10	CANADA	6063
GS10A	ASTM	6063
GS10B	ASTM	6101
GS11A	ASTM	6061
GS11B	ASTM	6053
GS11C	ASTM	6062
GS11N	CANADA	6061
GS11P	CANADA	6053
GS11R	CANADA	6351
GS31A	ASTM	....
GS42A	ASTM	B514.0
GZ42A	ASTM	A514.0
H11	ENGLAND	6011
H11	ENGLAND	6066
H12	ENGLAND	2618
H14	ENGLAND	2017
H15	ENGLAND	2014
H18	ENGLAND	2618
H19	ENGLAND	....
H2	ENGLAND	4047
H20	ENGLAND	6061
H30	ENGLAND	6351
H57S	ALCAN	5557
H9	ENGLAND	6063
HC1S	US	1270

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
HIDUMINIUM 00	ENGLAND	....
HIDUMINIUM 10	ENGLAND	413.0
HIDUMINIUM 90	ENGLAND	520.0
HIDUMINIUM Y	ENGLAND	242.0
HO124	GERMANY	A332.0
HONALIUM 10	GERMANY	520.0
HONALIUM 5	GERMANY	A514.0
HONALIUM 51	GERMANY	514.0
HONALIUM 511	GERMANY	514.0
HUETTAL 230	GERMANY	413.0
HUETTAL 240/10	GERMANY	520.0
HZM100	US	7001
INAFONT 25F	ITALY	D712.0
INAFONT C12T	ITALY	222.0
INAFONT C41	ITALY	295.0
INAFONT C45	ITALY	B295.0
INAFONT C8	ITALY	....
INAFONT S.10	ITALY	....
INAFONT S.13	ITALY	413.0
INAFONT S.52	ITALY	355.0
INAFONT S.7	ITALY	356.0
INAFONT S5	ITALY	355.0
INAFONT S5.5	ITALY	....
INJECTA C181	SWISS	356.0
J51S	US	6951
J57S	ALCAN	5357
JC1S	US	1075
K112	US	8112
K143	US	4343
K145	US	4043
K155	US	5005
K157	US	5357
K160	US	6951
K162	US.	6003
K186	US	5086
K57S	ALCAN	5050
L102	ENGLAND	2024
L103	ENGLAND	2024
L104	ENGLAND	2024
L105	ENGLAND	2024
L106	ENGLAND	2024
L107	ENGLAND	2024
L108	ENGLAND	2024
L111	ENGLAND	6082
L112	ENGLAND	6082
L113	ENGLAND	6082
L114	ENGLAND	6082
L115	ENGLAND	6082
L116	ENGLAND	1200
L16	ENGLAND	1200
L160	ENGLAND	7075
L161	ENGLAND	7075
L162	ENGLAND	7075
L163	ENGLAND	2014 (CLAD)
L164	ENGLAND	2014 (CLAD)

Information Handling Services, 2000

DATE: 12/23/88
ALUMINUM

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
L165	ENGLAND	2014 (CLAD)
L166	ENGLAND	2014 (CLAD)
L167	ENGLAND	2014 (CLAD)
L168	ENGLAND	2014
L17	ENGLAND	1200
L25	ENGLAND	2218
L33	ENGLAND	A413.0
L34	ENGLAND	1200
L36	ENGLAND	1200
L37	ENGLAND	2014
L4	ENGLAND	....
L42	ENGLAND	2618
L44	ENGLAND	5251
L53	ENGLAND	520.0
L54	ENGLAND	1200
L55	ENGLAND	5051
L56	ENGLAND	5051
L57S	ALCAN	5657
L58	ENGLAND	5556
L59	ENGLAND	3103
L60	ENGLAND	3103
L61	ENGLAND	3103
L62	ENGLAND	2014
L63	ENGLAND	2014
L64	ENGLAND	2014
L65	ENGLAND	2014
L65	ENGLAND	2014 EXT
L67	ENGLAND	1200
L70	ENGLAND	2014
L71	ENGLAND	2014
L72	ENGLAND	2014 (CLAD)
L73	ENGLAND	2014 (CLAD)
L75	ENGLAND	A413
L76	ENGLAND	2014
L77	ENGLAND	2014
L78	ENGLAND	355.0
L80	ENGLAND	5251
L81	ENGLAND	5251
L82	ENGLAND	5039
L83	ENGLAND	2618
L84	ENGLAND	6066
L85	ENGLAND	6066
L86	ENGLAND	2117
L87	ENGLAND	2017
L89	ENGLAND	2014 (CLAD)
L90	ENGLAND	2014 (CLAD)
L93	ENGLAND	2014
L95	ENGLAND	7075
L97	ENGLAND	2024
L98	ENGLAND	2024
L99	ENGLAND	A356.0
LAUFAL60	SWISS	355.0
LK183	US	5083
LM10	ENGLAND	520.0
LM12	ENGLAND	222.0
LM13	ENGLAND	A332.0
LM14	ENGLAND	242.0
LM16	ENGLAND	355.0
LM18	ENGLAND	443.0
LM18	ENGLAND	B443.0
LM20	ENGLAND	A413.0
LM24	ENGLAND	380.0
LM24	ENGLAND	A380.0
LM6	ENGLAND	413.0
LM6	ENGLAND	A413.0
LO-EX	ENGLAND	A332.0
LO-EX	ITALY	A332.0
LUBRAL SN6	ITALY	A850.0
M14	AUSTRIA	520.0
M1A	ASTM	3003
M75S	ALCAN	7080
MC10	CANADA	3003
MG11A	ASTM	3004
MG7	ENGLAND	518.0
MN105	AUSTRALIA	514.0
MN106	AUSTRALIA	A413.0
MN110	AUSTRALIA	520.0
MN113	AUSTRALIA	A332.0
MN114	AUSTRALIA	242.0
MN135	AUSTRALIA	356.0
MN143	AUSTRALIA	A380.0
MN143B	AUSTRALIA	....
N21	ENGLAND	4043
N3	ENGLAND	3003
N4	ENGLAND	....
N5	ENGLAND	5039
N51	ENGLAND	5454
N6	ENGLAND	5556
N7	ENGLAND	5556
N8	ENGLAND	5083
PERALUMAN 10	ITALY	520.0
PERALUMAN 10G	GERMANY	520.0
PERALUMAN 9	SWISS	514.0
PERCEDENT 71A	US	771.0
PERCEDENT 71B	US	B771.0
PRESSOFONT S5C	ITALY	....
PRESSOFONT S9CF	ITALY	380.0
R301	US	ALCLAD 2014
R305	US	5005
R306	US	6003
R308	US	1130
R399	US	8099
R995	US	1235
R998	US	1080
REDX-8	US	328.0
RR-58	ENGLAND	2618
S12	CANADA	4047
S12A	ASTM	A413.0
S12B	ASTM	413.0
S12P	CANADA	A413.0

Information Handling Services, 2000

DATE: 12/23/88
ALUMINUM

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
S20	AUSTRIA	356.0
S21	AUSTRIA	355.0
S22	AUSTRIA	A332.0
S250	ALCAN	238.0
S5	CANADA	4043
S5	CANADA	443.0
S5A	ASTM	B443.0
S5B	ASTM	443.0
S5B(0.30CU)	ASTM	A443.0
S5C	ASTM	C443.0
S7A	ASTM	A444.0
SA1	ITALY	A332.0
SC102A	ASTM	383.0
SC103A	ASTM	F332.0
SC114A	ASTM	384.0
SC122A	ASTM	....
SC51	CANADA	355.0
SC51A	ASTM	355.0
SC51B	ASTM	C355.0
SC64C	ASTM	....
SC64D	ASTM	319.0
SC82A	ASTM	328.0
SC84	CANADA	380.0
SC84A	ASTM	A380.0
SC84B	ASTM	380.0
SC92A	ASTM	354.0
SC94A	ASTM	333.0
SG100A	ASTM	A360.0
SG100B	ASTM	360.0
SG11A	ASTM	6151
SG11B	ASTM	6066
SG11P	CANADA	6151
SG121	CANADA	4032
SG121A	ASTM	4032
SG70A	ASTM	356.0
SG70B	ASTM	A356.0
SG71A	ASTM	357.0
SG91A	ASTM	359.0
SILAPONT NORMALE	ITALY	A413.0
SILUMAN	GERMANY	413.0
SN122	CANADA	A332.0
SN122A	ASTM	A332.0
STANTUFONT NORMALE	ITALY	A332.0
TENZALLOY	US	713.0
TERMAFONT C2	ITALY	222.0
TERMAFONT S122	ITALY	A332.0
TERMAFONT Y	ITALY	242.0
TERMAFONT YT	ITALY	242.0
TERNALLOY 5	US	705.0
TERNALLOY 7	US	707.0
UNIFONT 5	GERMANY	S712.0
UNIFONT 5	SWISS	S712.0
VANASIL	US	393.0
WILMIL	ENGLAND	413.0
X149	US	249.0

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
X47S	US	4047
X64S	US	X6064
X79S	US	7079
XA5S	US	3005
XA78S	US	7178
XB14S	US	2214
XB51S	US	X6251
XB80S	US	8280
XC56S	US	5356
XC750	US	XC850.0
XD50S	US	5405
XE43S	US	4543
Y	ENGLAND	242.0
Y	GERMANY	242.0
Y	ITALY	242.0
YTI	ITALY	242.0
Z1	AUSTRIA	D712.0
Z132	US	Z332.0
Z55S	ALCAN	6253
ZC60A	ALCAN	C712.0
ZC81A	ASTM	713.0
ZC81B	ASTM	....
ZG32A	ASTM	705.0
ZG42A	ASTM	707.0
ZG61	CANADA	D712.0
ZG61A	ASTM	D712.0
ZG61B	ASTM	D712.0
ZG62	CANADA	7075
ZG62A	ASTM	7075
ZG71B	ASTM	771.0

Information Handling Services, 2000

TABLE 4B

STEEL

Information Handling Services, 2000

DATE: 12/23/88
STEEL

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
040A20	ENGLAND	1020
060A35	ENGLAND	1035
060A47	ENGLAND	1043
060A62	ENGLAND	1060
060A96	ENGLAND	1095
070M20	ENGLAND	1020
080A32	ENGLAND	1035
080A35	ENGLAND	1035
080A37	ENGLAND	1035
080A40	ENGLAND	1040
080H46	ENGLAND	1043
080M36	ENGLAND	1035
080M40	ENGLAND	1043
080M46	ENGLAND	1043
1..4104	GERMANY	430F
1..7223	GERMANY	4142H
1.0204	GERMANY	1008
1.0311	GERMANY	1006
1.0312	FRANCE	1005
1.0313	GERMANY	1006
1.0314	GERMANY	1005
1.0402	GERMANY	1020
1.0419	GERMANY	1016
1.0501	GERMANY	1035
1.0503	GERMANY	1043
1.0601	GERMANY	1060
1.0647	GERMANY	1084
1.0702	GERMANY	1110
1.0711	GERMANY	1212
1.0715	GERMANY	1213
1.0718	GERMANY	12L14
1.0726	GERMANY	1140
1.0727	GERMANY	1146
1.0909	GERMANY	9260
1.0909	GERMANY	9260H
1.0912	GERMANY	1345
1.0912	GERMANY	1345H
1.1121	GERMANY	1010
1.1133	GERMANY	1022
1.1133	GERMANY	1522H
1.1141	GERMANY	1015
1.1141	GERMANY	1017
1.1151	GERMANY	1023
1.1157	GERMANY	1039
1.1158	GERMANY	1025
1.1160	GERMANY	1524
1.1160	GERMANY	1524H
1.1161	GERMANY	1526
1.1161	GERMANY	1527
1.1165	GERMANY	1330
1.1165	GERMANY	1330H
1.1167	GERMANY	1335
1.1167	GERMANY	1335H
1.1167	GERMANY	1541
1.1167	GERMANY	1541H

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
1.1172	GERMANY	1030
1.1176	GERMANY	1038
1.1176	GERMANY	1038H
1.1186	GERMANY	1040
1.1191	GERMANY	1042
1.1191	GERMANY	1045
1.1191	GERMANY	1045H
1.1201	GERMANY	1049
1.1209	GERMANY	1055
1.1210	GERMANY	1050
1.1226	GERMANY	1548
1.1226	GERMANY	1552
1.1231	GERMANY	1070
1.1248	GERMANY	1078
1.1260	GERMANY	1566
1.1273	GERMANY	1090
1.1274	GERMANY	1095
1.2080	GERMANY	D3
1.2210	GERMANY	L2
1.2330	GERMANY	P20
1.2341	GERMANY	P4
1.2343	GERMANY	H11
1.2344	GERMANY	H13
1.2363	GERMANY	A2
1.2365	GERMANY	H10
1.2379	GERMANY	D2
1.2510	GERMANY	01
1.2550	GERMANY	S1
1.2581	GERMANY	H21
1.2606	GERMANY	H12
1.2625	GERMANY	H23
1.2713	GERMANY	L6
1.2735	GERMANY	P6
1.2842	GERMANY	02
1.3202	GERMANY	T15
1.3246	GERMANY	M41
1.3247	GERMANY	M42
1.3249	GERMANY	M33
1.3249	GERMANY	M34
1.3255	GERMANY	T4
1.3265	GERMANY	T5
1.3342	GERMANY	M3CLASS1
1.3343	GERMANY	M2
1.3344	GERMANY	M3CLASS2
1.3346	GERMANY	M1
1.3348	GERMANY	M7
1.3355	GERMANY	T1
1.3503	GERMANY	E51100
1.3505	GERMANY	E52100
1.4000	GERMANY	410
1.4002	GERMANY	405
1.4002	GERMANY	409
1.4005	GERMANY	416
1.4006	GERMANY	410
1.4016	GERMANY	430

Information Handling Services, 2000

DATE: 12/23/88
STEEL

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
1.40160	GERMANY	430
1.4021	GERMANY	420
1.4024	GERMANY	403
1.4031	GERMANY	430
1.4034	GERMANY	420
1.4057	GERMANY	431
1.4104	GERMANY	430F
1.4112	GERMANY	440B
1.4113	GERMANY	434
1.4125	GERMANY	440C
1.4301	GERMANY	304
1.4303	GERMANY	305
1.4303	GERMANY	308
1.4305	GERMANY	303
1.4306	GERMANY	304L
1.4310	GERMANY	301
1.4311	GERMANY	304LN
1.4371	GERMANY	202
1.4401	GERMANY	316
1.4404	GERMANY	316L
1.4406	GERMANY	316LN
1.4429	GERMANY	316LN
1.4435	GERMANY	316L
1.4436	GERMANY	316
1.4438	GERMANY	317
1.4438	GERMANY	317L
1.4449	GERMANY	317
1.4454	GERMANY	A286
1.4460	GERMANY	329
1.4510	GERMANY	430
1.4512	GERMANY	409
1.4532	GERMANY	632
1.45334.6	GERMANY	PH13-8MO H950
1.4541	GERMANY	321
1.4544	GERMANY	321
1.4546	GERMANY	348
1.4550	GERMANY	347
1.4564.9	GERMANY	17-7PH
1.4568	GERMANY	17-7PH TH1050
1.4828	GERMANY	309
1.4833	GERMANY	309S
1.4841	GERMANY	310
1.4841	GERMANY	314
1.4935	GERMANY	422
1.49448	GERMANY	A286
1.4980	GERMANY	660
1.5069	GERMANY	1340H
1.5411	GERMANY	4032
1.5411	GERMANY	4032/4037
1.5411	GERMANY	4037
1.5415	GERMANY	40227
1.5415	GERMANY	4027/4028
1.5415	GERMANY	4028
1.5416	GERMANY	4023
1.5418	GERMANY	4012

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
1.5419	GERMANY	4027/4028
1.5523	GERMANY	15B21H
1.5527	GERMANY	15B41H
1.6523	GERMANY	8615
1.6523	GERMANY	8617
1.6523	GERMANY	8617H
1.6523	GERMANY	8620
1.6523	GERMANY	8620H
1.6543	GERMANY	8615
1.6543	GERMANY	8622
1.6543	GERMANY	8622H
1.6543	GERMANY	8720
1.6543	GERMANY	8720H
1.6543	GERMANY	8822
1.6543	GERMANY	8822H
1.6545	GERMANY	8615
1.6545	GERMANY	8630
1.6545	GERMANY	8630H
1.6546	GERMANY	8637
1.6546	GERMANY	8640
1.6546	GERMANY	8640H
1.6546	GERMANY	8740
1.6546	GERMANY	8740H
1.6562	GERMANY	4340
1.6562	GERMANY	E4340
1.6562	GERMANY	E4340H
1.6565	GERMANY	4340
1.6565	GERMANY	4340H
1.7006	GERMANY	5140H
1.7006	GERMANY	5150
1.7007	GERMANY	50B40
1.7007	GERMANY	50B40H
1.7030	GERMANY	5130
1.7033	GERMANY	5130H
1.7033	GERMANY	5132
1.7034	GERMANY	5132H
1.7034	GERMANY	5135
1.7035	GERMANY	5135H
1.7035	GERMANY	5140
1.7138	GERMANY	50B50
1.7138	GERMANY	50B50H
1.7147	GERMANY	5120
1.7147	GERMANY	5120H
1.7176	GERMANY	5155
1.7176	GERMANY	5155H
1.7218	GERMANY	4118
1.7218	GERMANY	4130
1.7218	GERMANY	4130/4135/4118
1.7218	GERMANY	4130H
1.7218	GERMANY	4135
1.7220	GERMANY	4118
1.7220	GERMANY	4130
1.7220	GERMANY	4130/4135/4118
1.7220	GERMANY	4135
1.7220	GERMANY	4135H

Information Handling Services, 2000

DATE: 12/23/88
STEEL

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
1.7223	GERMANY	4142H
1.7225	GERMANY	4137
1.7225	GERMANY	4137H
1.7225	GERMANY	4140
1.7225	GERMANY	4140/4137
1.7225	GERMANY	4140H
1.7226	GERMANY	4150
1.7227	GERMANY	4142
1.7227	GERMANY	4145
1.7227	GERMANY	4147
1.7227	GERMANY	4147/4145/4142
1.7228	GERMANY	4147
1.7228	GERMANY	4147H
1.7228	GERMANY	4150
1.7228	GERMANY	4150/4161
1.7228	GERMANY	4150H
1.7228	GERMANY	4161
1.7266	GERMANY	4150/4161
1.7266	GERMANY	4161
1.7335	GERMANY	4118
1.7335	GERMANY	4130
1.7335	GERMANY	4130/4118/4135
1.7335	GERMANY	4135
1.7511	GERMANY	6118
1.7511	GERMANY	6118H
1.8159	GERMANY	6150
1.8159	GERMANY	6150H
100C6	FRANCE	52100
100C6	FRANCE	E52100
100CR6	ITALY	E52100
10S20	ITALY	1212
10X13CJU	RUSSIA	405
120M36	ENGLAND	1039
12CD	FRANCE	4135
12CD4	FRANCE	4118
12X13	RUSSIA	403
12X13	RUSSIA	410
12X17	RUSSIA	430
12X18N10E	RUSSIA	303
1370	SWEDEN	1015
1370	SWEDEN	1017
13CRMO4.4	GERMANY	4118
13CRMO4.4	GERMANY	4130
13CRMO4.4	GERMANY	4130/4135/4118
13CRMO4.4	GERMANY	4135
1450	SWEDEN	1020
150M36	ENGLAND	1039
1550	SWEDEN	1035
15CD.05	FRANCE	4130
15CD3.5	FRANCE	4130
15CD3.5	FRANCE	4130/4135/4118
15CD3.5	FRANCE	4135
15CD4.05	FRANCE	4130/4135/4135
15CD4.05	FRANCE	4135
15CRM05	GERMANY	4135

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
15CRMO5	GERMANY	4118
15CRMO5	GERMANY	4130
15CRMO5	GERMANY	4130/4135/4118
15MNMO53	GERMANY	4012
15MO3	GERMANY	4027
15MO3	GERMANY	4028
15NCD2	FRANCE	8615
1650	SWEDEN	1043
1660	SWEDEN	1049
1672	SWEDEN	1042
1672	SWEDEN	1045
1672	SWEDEN	1045H
1770	SWEDEN	1070
1774	SWEDEN	1078
1870	SWEDEN	1095
18CD4	FRANCE	4118
18CD4	FRANCE	4130
18CD4	FRANCE	4130/4135/4118
18MD4.05	FRANCE	4023
18NCD4	FRANCE	4718
1914	SWEDEN	12L14
1957	SWEDEN	1140
1973	SWEDEN	1146
20CD7	FRANCE	4320
20CRMO5	GERMANY	4118
20CRMO5	GERMANY	4130
20CRMO5	GERMANY	4130/4135/4118
20CRMO5	GERMANY	4135
20MC5	FRANCE	5120
20MC5	FRANCE	5120H
20MO3	GERMANY	4023
20NCD2	FRANCE	8615
20NCD2	FRANCE	8617
20NCD2	FRANCE	8617H
20NCD2	FRANCE	8620
20NCD2	FRANCE	8620H
20NICRMO2	ITALY	8617
20NICRMO2	ITALY	8617H
20NICRMO2	ITALY	8620
20NICRMO2	ITALY	8620H
20X13	RUSSIA	420
20X17N2	RUSSIA	431
2120	SWEDEN	1335
2120	SWEDEN	1335H
2120	SWEDEN	1541
2120	SWEDEN	1541H
220M07	ENGLAND	1213
2225	SWEDEN	4130
2225	SWEDEN	4130H
2230	SWEDEN	430
2230	SWEDEN	6150
2230	SWEDEN	6150H
2234	SWEDEN	4135
2234	SWEDEN	4135H
2242	SWEDEN	H13

Information Handling Services, 2000

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
2244	SWEDEN	4137
2244	SWEDEN	4137H
2244	SWEDEN	4140
2244	SWEDEN	4140H
2260	SWEDEN	A2
22NCD2	FRANCE	8617
22NCD2	FRANCE	8617H
22NCD2	FRANCE	8620
22NCD2	FRANCE	8620H
2301	SWEDEN	410
2302	SWEDEN	403
2302	SWEDEN	410
2303	SWEDEN	420
2316	SWEDEN	303
2321	SWEDEN	431
2324	SWEDEN	320
2325	SWEDEN	434
2331	SWEDEN	301
2332	SWEDEN	304
2337	SWEDEN	321
2338	SWEDEN	347
2346	SWEDEN	303
2347	SWEDEN	316
2348	SWEDEN	316L
2352	SWEDEN	304L
2353	SWEDEN	316L
2367	SWEDEN	317L
2371	SWEDEN	304LN
2375	SWEDEN	316LN
2380	SWEDEN	416
2383	SWEDEN	430F
250A58	ENGLAND	9260
250A58	ENGLAND	9260H
25CD4	FRANCE	4130
25CD4	FRANCE	4130H
25CD4S	FRANCE	4130
25CD4S	FRANCE	4130H
25CRMO4	ITALY	4130
25CRMO4	ITALY	4130H
25CRMO4KB	ITALY	4130
25CRMO4KB	ITALY	4130H
2722	SWEDEN	M2
2S.117	ENGLAND	5135H
2S.117	ENGLAND	5140
2S.119	ENGLAND	4340
2S.119	ENGLAND	4340H
2S.130	ENGLAND	348
2S.516	ENGLAND	1345
2S.516	ENGLAND	1345H
2S.517	ENGLAND	1345
2S.517	ENGLAND	1345H
2S.93	ENGLAND	1040
2S93	ENGLAND	1040
302S17	ENGLAND	304
303S21	ENGLAND	303

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
304S12	ENGLAND	304L
304S14	ENGLAND	304L
304S15	ENGLAND	304
304S16	ENGLAND	304
304S18	ENGLAND	304
304S22	ENGLAND	304L
304S25	ENGLAND	304
304S40	ENGLAND	304
30CD4	FRANCE	4118
30CD4	FRANCE	4130
30CD4	FRANCE	4130/4135/4118
30CD4	FRANCE	4135
30CRMO2KB	ITALY	8630
30NCD2	FRANCE	8615
30NICRMO22	GERMANY	8615
310S24	ENGLAND	310
310S24	ENGLAND	314
3111TYPE6	ENGLAND	4340
3111TYPE6	ENGLAND	4340H
316S12	ENGLAND	316L
316S14	ENGLAND	316L
316S16	ENGLAND	316
316S18	ENGLAND	316
316S22	ENGLAND	316L
316S24	ENGLAND	316L
316S25	ENGLAND	316
316S26	ENGLAND	316
316S29	ENGLAND	316L
316S30	ENGLAND	316
316S30	ENGLAND	316L
316S31	ENGLAND	316L
316S37	ENGLAND	316L
316S40	ENGLAND	316
316S41	ENGLAND	316
316S82	ENGLAND	316L
317S12	ENGLAND	317L
321S12	ENGLAND	321
321S18	ENGLAND	321
321S22	ENGLAND	321
321S27	ENGLAND	321
321S40	ENGLAND	321
321S49	ENGLAND	321
321S50	ENGLAND	321
321S59	ENGLAND	321
321S87	ENGLAND	321
323	SAE	17-7PH
32C4	FRANCE	5130
32C4	FRANCE	5132
32DCV28	FRANCE	H10
347S17	ENGLAND	347
347S17	ENGLAND	348
347S18	ENGLAND	348
347S40	ENGLAND	348
34CR4KB	ITALY	5130H
34CR4KB	ITALY	5132

MSFC-HDBK-527 REV F 9999942 0007200 8

Information Handling Services, 2000

DATE: 12/23/88
STEEL

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
34CRMO4KB	ITALY	4135
34CRMO4KB	ITALY	4135H
34CRMOS4	GERMANY	4130
34CRMOS4	GERMANY	4137
34CRMOS4	GERMANY	4140
34CRMOS4	GERMANY	4140/4130
34CRMOS4	GERMANY	4140/4137
35CD4	FRANCE	4118
35CD4	FRANCE	4130
35CD4	FRANCE	4135
35CD4	FRANCE	4135/4130/4118
35CD4	FRANCE	4135H
35CD4TS	FRANCE	4135
35CD4TS	FRANCE	4135H
35CRMO4	ITALY	4135
35CRMO4	ITALY	4135H
35CRMO4F	ITALY	4135
35CRMO4F	ITALY	4135H
35M5	FRANCE	1039
35M5	FRANCE	1140
35MNMO5	GERMANY	4032/4037
35MNO5	GERMANY	4032
35MNO5	GERMANY	4037
35NCD2	FRANCE	8637
38C4	FRANCE	5132H
38C4	FRANCE	5135
38CR4KB	ITALY	5132H
38CR4KB	ITALY	5135
38CRB1KB	ITALY	50B40
38CRB1KB	ITALY	50B40H
38CRMO4	ITALY	4142H
38CRMO4KB	ITALY	4137
38CRMO4KB	ITALY	4137H
38CRMO4KB	ITALY	4140
38CRMO4KB	ITALY	4140H
3FMF5	FRANCE	1140
3ONICRMO2KB	ITALY	8630
3S.61	ENGLAND	410
3S.62	ENGLAND	420
3S.95	ENGLAND	4340
3S.95	ENGLAND	4340H
3X17N14M2	RUSSIA	304L
3X17N14M2	RUSSIA	316L
3X18N11	RUSSIA	304L
3X18N11	RUSSIA	304LN
405S17	ENGLAND	405
409S17	ENGLAND	409
40CD4	FRANCE	4137
40CD4	FRANCE	4137H
40CD4	FRANCE	4140
40CD4	FRANCE	4140/4137
40CD4	FRANCE	4140H
40CD49	FRANCE	4137
40CR4	ITALY	5140
40CRMO4	ITALY	4137
40CRMO4	ITALY	4137H
40CRMO4	ITALY	4140
40CRMO4	ITALY	4140H
40M5	FRANCE	1335
40M5	FRANCE	1335H
40M5	FRANCE	1541
40M5	FRANCE	1541H
40M59	FRANCE	1541
40MNMO43	GERMANY	4042
40MNMO43	GERMANY	4042/4047
40MNMO43	GERMANY	4047
40NCD2	FRANCE	8637
40NCD2TS	FRANCE	8637
40NICRMO22	GERMANY	8637
40NICRMO2KB	ITALY	8640
40NICRMO2KB	ITALY	8640H
40NICRMO2KB	ITALY	8740
40NICRMO2KB	ITALY	8740H
40NICRMO7	ITALY	E4340H
40NICRMO7	JAPAN	E4340
40NICRMO73	GERMANY	4340
40NICRMO7KB	ITALY	E4340H
40NICRMO7KB	JAPAN	E4340
410S21	ENGLAND	410
416S21	ENGLAND	416
41CR4KB	ITALY	5135H
41CR4KB	ITALY	5140
420S29	ENGLAND	403
420S37	ENGLAND	420
42C2	FRANCE	5140H
42C2	FRANCE	5150
42C4	FRANCE	5135H
42C4	FRANCE	5140
42CD4	FRANCE	4137
42CD4	FRANCE	4137H
42CD4	FRANCE	4140
42CD4	FRANCE	4140/4137
42CD4	FRANCE	4140H
42CD4	FRANCE	4142
42CD4	FRANCE	4142/4145/4147
42CD4	FRANCE	4145
42CD4	FRANCE	4147
42CRMOS4	GERMANY	4142
42CRMOS4	GERMANY	4142/4147/4145
42CRMOS4	GERMANY	4145
42CRMOS4	GERMANY	4147
430S15	ENGLAND	430
431S29	ENGLAND	431
434S19	ENGLAND	434
45C2	FRANCE	5140
45C29	FRANCE	5150
45MF4	FRANCE	1146
5010D	AMS	1212
5024C	AMS	1137
5024C	ENGLAND	1137

Information Handling Services, 2000

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
5032	AMS	1020
5032	ENGLAND	1020
5040	AMS	1010
5042	AMS	1010
5044	AMS	1010
5045	AMS	1020
5047	AMS	1010
5053	AMS	1010
5060	AMS	1015
5069	AMS	1018
5070	AMS	1022
5075	AMS	1025
5077	AMS	1025
5080	AMS	1035
5082	AMS	1035
5085	AMS	1050
50CRMO4	GERMANY	4150
50CRMO4	GERMANY	4150/4161
50CRMO4	GERMANY	4161
50CRV4	ITALY	6150
50CRV4	ITALY	6150H
50CV4	FRANCE	6150
50CV4	FRANCE	6150H
5110	AMS	1080
5112	AMS	1090
5115	AMS	1070
5121	AMS	1095
5122	AMS	1095
5132	AMS	1095
530A36	ENGLAND	5135
530A40	ENGLAND	5135H
530A40	ENGLAND	5140
530H30	ENGLAND	5130
530H32	ENGLAND	5130H
530H32	ENGLAND	5132
530H36	ENGLAND	5132H
530H36	ENGLAND	5135
530H40	ENGLAND	5135H
530H40	ENGLAND	5140
530M40	ENGLAND	5135H
530M40	ENGLAND	5140
530S30	ENGLAND	5130
530S32	ENGLAND	5130H
530S32	ENGLAND	5132
530S36	ENGLAND	5132H
5331	AMS	4340
5333	AMS	8615
5342	AMS	630
5343	AMS	630
5344	AMS	630
534A99	ENGLAND	E52100
5355	AMS	630
535A99	ENGLAND	E52100
5501	AMS	304
5503	AMS	430

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
5504	AMS	410
5505	AMS	410
5506	AMS	420
5507	AMS	316L
5510	AMS	321
5511	AMS	304L
5512	AMS	347
5513	AMS	304
5514	AMS	305
5515	AMS	302
5516	AMS	302
5517	AMS	301
5518	AMS	301
5519	AMS	301
5520	AMS	632
5521	AMS	310S
5522	AMS	314
5523	AMS	309S
5524	AMS	316
5525	AMS	660
5528	AMS	631
5529	AMS	631
5546	AMS	633
5547	AMS	634
5548	AMS	633
5549	AMS	634
5554	AMS	633
5556	AMS	347
5557	AMS	321
5558	AMS	347
5559	AMS	321
5560	AMS	304
5565	AMS	304
5566	AMS	304
5567	AMS	304
5568	AMS	631
5570	AMS	321
5571	AMS	347
5572	AMS	310S
5573	AMS	316
5574	AMS	309S
5575	AMS	347
5576	AMS	321
5577	AMS	310S
5591	AMS	410
5592	AMS	330
5594	AMS	634
55C3	FRANCE	5155
55C3	FRANCE	5155H
55C39	FRANCE	5155H
55NCOV7	FRANCE	L6
55WC20	FRANCE	S1
5604	AMS	630
5610	AMS	416SE
5611	AMS	403

MSFC-HDBK-527 REV F ■ 9999942 0007202 1 ■

Information Handling Services, 2000

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
5612	AMS	403
5613	AMS	410
5615	AMS	414
5618	AMS	440C
5620	AMS	420F
5621	AMS	420
5622	AMS	630
5626	AMS	T1
5627	AMS	430
5628	AMS	431
5630	AMS	440C
5631	AMS	440A
5636	AMS	302
5637	AMS	302
5639	AMS	304
5640(1)	AMS	303
5640(TYPE2)	AMS	303SE
5641	AMS	303SE
5643	AMS	630
5644	AMS	631
5645	AMS	321
5646	AMS	347
5647	AMS	304L
5648	AMS	316
5649	AMS	316F
5650	AMS	309S
5651	AMS	310S
5652	AMS	314
5653	AMS	316L
5654	AMS	347
5655	AMS	422
5657	AMS	632
5673	AMS	631
5674	AMS	347
5678	AMS	631
5680	AMS	347
5685	AMS	305
5686	AMS	305
5688	AMS	302
5689	AMS	321
5690	AMS	316
5691	AMS	316
5694	AMS	310
5695	AMS	310
5697	AMS	304
5716	AMS	330
5731	AMS	660
5732	AMS	660
5734	AMS	660
5735	AMS	660
5736	AMS	660
5737	AMS	660
5738	AMS	303SE
5743	AMS	634
5744	AMS	634

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
5745	AMS	633
5774	AMS	633
5776	AMS	410
5780	AMS	634
5804	AMS	660
5805	AMS	660
5812	AMS	632
5813	AMS	632
5821	AMS	410
5824	AMS	631
5825	AMS	630
58CRMNMO443	GERMANY	4150
58CRMNMO443	GERMANY	4150/4160
58CRMNO443	GERMANY	41610
58WCR9KU	ITALY	S1
5S.80	ENGLAND	431
60S7	FRANCE	9260
60S7	FRANCE	9260H
61SC7	FRANCE	9260
61SC7	FRANCE	9260H
6272	AMS	8617
6274	AMS	8620
6275	AMS	94B17
6275A	AMS	94B15
6276	AMS	8620
6277	AMS	8620
6280	AMS	8630
6281	AMS	8630
6290	AMS	4615
6294	AMS	4620
6322	AMS	8740
6325	AMS	8740
6327	AMS	8740
6350	AMS	4130
6355	AMS	863
6356	AMS	4130
6358	AMS	8740
6359	AMS	4340
6360	AMS	4130
6361	AMS	4130
6362	AMS	4130
6365C	AMS	4135
6370	AMS	4130
6371	AMS	4130
6372C	AMS	4135
6373	AMS	4130
6381	AMS	4140
6382	AMS	4140
6390	AMS	4140
6395	AMS	4140
6414	AMS	4340
6415	AMS	4340
6437	AMS	H11
6440	AMS	E52100
6443	AMS	E51100

Information Handling Services, 2000

DATE: 12/23/88
STEEL

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
6444	AMS	E52100
6446	AMS	E51100
6447	AMS	E52100
6448	AMS	6150
6449	AMS	E51100
6450	AMS	6150
6455	AMS	6150
6485	AMS	H11
6487	AMS	H11
6488	AMS	H11
6530	AMS	8630
6550	AMS	8630
6X18N11	RUSSIA	305
70840	ENGLAND	4140
708A37	ENGLAND	4135
708A37	ENGLAND	4135H
708A40	ENGLAND	4137H
708A42	ENGLAND	4137
708A42	ENGLAND	4137H
708A42	ENGLAND	4140
708A42	ENGLAND	4140H
708M40	ENGLAND	4137
708M40	ENGLAND	4140H
709A40	ENGLAND	4137H
709M40	ENGLAND	4137
709M40	ENGLAND	4140
709M40	ENGLAND	4140H
7240	AMS	1060
7301	AMS	6150
7304	AMS	1095
735A50	ENGLAND	6150
735A50	ENGLAND	6150H
80520	ENGLAND	8622H
80520	ENGLAND	8822H
805A20	ENGLAND	8622
805A20	ENGLAND	8720
805A20	ENGLAND	8720H
805A20	ENGLAND	8822
805H20	ENGLAND	8617
805H20	ENGLAND	8617H
805H20	ENGLAND	8620
805H20	ENGLAND	8620H
805M20	ENGLAND	8617
805M20	ENGLAND	8617H
805M20	ENGLAND	8620
805M20	ENGLAND	8620H
817M40	ENGLAND	4340
817M40	ENGLAND	4340H
88MNV8KU	ITALY	02
8X13	RUSSIA	410S
8X17T	RUSSIA	430TI
8X18N10T	RUSSIA	321
8X18N12B	RUSSIA	347
90MV8	FRANCE	02
95X18	RUSSIA	440C

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
9SMN23	ITALY	1213
9SMNPB23	ITALY	12L14
A107	ASME	1213
A107(B1113)	ASME	1213
A108	ASME	1213
A108(B1113)	ASME	1213
ANC1GRADEA	ENGLAND	410
ANC3GRADEB	ENGLAND	347
BA2	ENGLAND	A2
BD2	ENGLAND	D2
BD3	ENGLAND	D3
BH11	ENGLAND	H11
BH12	ENGLAND	H12
BH13	ENGLAND	H13
BH21	ENGLAND	H21
BM1	ENGLAND	M1
BM2	ENGLAND	M2
BM34	ENGLAND	M33
BM34	ENGLAND	M34
BM42	ENGLAND	M42
BO1	ENGLAND	O1
BO2	ENGLAND	O2
BT1	ENGLAND	T1
BT15	ENGLAND	T15
BT4	ENGLAND	T4
BT5	ENGLAND	T5
C20	ITALY	1020
C35	ITALY	1035
C45	ITALY	1043
C60	ITALY	1060
CB10FU	ITALY	1008
CB35	ITALY	1030
CC20	FRANCE	1020
CC35	FRANCE	1035
CC45	FRANCE	1043
CC55	FRANCE	1060
CDS105/106	ENGLAND	1039
CDS110	ENGLAND	4130
CDS110	ENGLAND	4130H
CDS18	ENGLAND	420
CDS20	ENGLAND	321
DIN17200	GERMANY	4142
DIN17200	GERMANY	4142/4145/4147
DIN17200	GERMANY	4145
DIN17200	GERMANY	4147
EN.44B	ENGLAND	1095
EN.47	ENGLAND	6150
EN.47	ENGLAND	6150H
EN.56A	ENGLAND	410
EN.56B	ENGLAND	403
EN.56C	ENGLAND	420
EN.58B	ENGLAND	321
EN.58C	ENGLAND	321
EN.58E	ENGLAND	304
EN.58F	ENGLAND	347

Information Handling Services, 2000

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
EN.58G	ENGLAND	347
EN.58H	ENGLAND	316
FD5	FRANCE	1005
FDTU4	FRANCE	1008
G22MN3	ITALY	1022
G22MN3	ITALY	1522H
G40CRMO4	ITALY	4137
G40CRMO4	ITALY	4137H
G40CRMO4	ITALY	4140
G40CRMO4	ITALY	4140H
H34.30	ANSI	330
H34.31	ANSI	330
ICL472T	ITALY	321
M40	GERMANY	4140
S.139	ENGLAND	E4340
S.139	ENGLAND	E4340H
S.141	ENGLAND	410
S.525	ENGLAND	348
S.527	ENGLAND	348
S.536	ENGLAND	304L
S.537	ENGLAND	316L
S10C	JAPAN	1010
S12C	JAPAN	1010
S15C	JAPAN	1015
S15C	JAPAN	1017
S15CK	JAPAN	1015
S15CK	JAPAN	1017
S17C	JAPAN	1015
S17C	JAPAN	1017
S20C	JAPAN	1023
S20CK	JAPAN	1023
S22C	JAPAN	1023
S25C	JAPAN	1025
S28C	JAPAN	1025
S40C	JAPAN	1040
S45C	JAPAN	1042
S45C	JAPAN	1045
S45C	JAPAN	1045H
S48C	JAPAN	1042
S48C	JAPAN	1045
S48C	JAPAN	1045H
S50C	JAPAN	1049
S53C	JAPAN	1050
S55C	JAPAN	1050
S9CK	JAPAN	1010
SA182	ASME	304
SA182	ASME	304L
SA182	ASME	304N
SA182	ASME	310
SA182	ASME	316
SA182	ASME	316L
SA182	ASME	316N
SA182	ASME	321
SA182	ASME	347
SA182	ASME	348

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
SA182	ASME	429
SA182	ASME	430
SA193	ASME	305
SA193	ASME	316
SA193	ASME	321
SA193	ASME	347
SA194	ASME	303
SA194	ASME	303SE
SA194	ASME	305
SA194	ASME	316
SA194	ASME	321
SA194	ASME	347
SA194	ASME	416
SA194	ASME	416SE
SA194(6)	ASME	410
SA194(8)	ASME	304
SA213	ASME	304
SA213	ASME	304L
SA213	ASME	304N
SA213	ASME	310
SA213	ASME	316
SA213	ASME	316L
SA213	ASME	316N
SA213	ASME	321
SA213	ASME	347
SA213	ASME	348
SA240	ASME	302
SA240	ASME	304
SA240	ASME	304L
SA240	ASME	304N
SA240	ASME	305
SA240	ASME	309S
SA240	ASME	310S
SA240	ASME	316
SA240	ASME	316L
SA240	ASME	316N
SA240	ASME	317
SA240	ASME	317L
SA240	ASME	321
SA240	ASME	347
SA240	ASME	348
SA240	ASME	405
SA240	ASME	410
SA240	ASME	430
SA240	ASTM	429
SA249	ASME	304
SA249	ASME	304L
SA249	ASME	304N
SA249	ASME	309
SA249	ASME	310
SA249	ASME	316
SA249	ASME	316L
SA249	ASME	316N
SA249	ASME	317
SA249	ASME	321

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0007205 7

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
SA249	ASME	347
SA249	ASME	348
SA268	ASME	329
SA268	ASME	405
SA268	ASME	409
SA268	ASME	410
SA268	ASME	429
SA268	ASME	430
SA268	ASME	446
SA312	ASME	304
SA312	ASME	304L
SA312	ASME	304N
SA312	ASME	309
SA312	ASME	310
SA312	ASME	316
SA312	ASME	316L
SA312	ASME	316N
SA312	ASME	317
SA312	ASME	321
SA312	ASME	347
SA312	ASME	348
SA320	ASME	303
SA320	ASME	303SE
SA320	ASME	316
SA320	ASME	321
SA320	ASME	347
SA320(B8)	ASME	304
SA358	ASME	304
SA358	ASME	304N
SA358	ASME	309
SA358	ASME	310
SA358	ASME	316
SA358	ASME	316N
SA358	ASME	321
SA358	ASME	347
SA358	ASME	348
SA376	ASME	304
SA376	ASME	304N
SA376	ASME	316
SA376	ASME	316N
SA376	ASME	321
SA376	ASME	347
SA376	ASME	348
SA403	ASME	304
SA403	ASME	304L
SA403	ASME	309
SA403	ASME	310
SA403	ASME	316
SA403	ASME	316L
SA403	ASME	316N
SA403	ASME	317
SA403	ASME	321
SA403	ASME	347
SA403	ASME	348
SA409	ASME	304
SA409	ASME	309
SA409	ASME	310
SA409	ASME	316
SA409	ASME	317
SA409	ASME	321
SA409	ASME	347
SA409	ASME	348
SA412	ASME	201
SA430	ASME	304
SA430	ASME	304N
SA430	ASME	316
SA430	ASME	316N
SA430	ASME	321
SA430	ASME	347
SA479	ASME	302
SA479	ASME	304
SA479	ASME	304L
SA479	ASME	304N
SA479	ASME	310S
SA479	ASME	316
SA479	ASME	316L
SA479	ASME	316N
SA479	ASME	321
SA479	ASME	347
SA479	ASME	348
SA479	ASME	405
SA479	ASME	410
SA479	ASME	430
SA564	ASME	630
SA638	ASME	660
SA688	ASME	304
SA688	ASME	304L
SA688	ASME	316
SA688	ASME	316L
SA705	ASME	630
SA705	ASME	631
SCCRM1	JAPAN	4130
SCCRM1	JAPAN	4130H
SCCRM3	JAPAN	4135
SCCRM3	JAPAN	4135H
SCM1	JAPAN	4135
SCM1	JAPAN	4135H
SCM2	JAPAN	4130
SCM2	JAPAN	4130H
SCM4	JAPAN	4137
SCM4	JAPAN	4137H
SCM4	JAPAN	4140
SCM4	JAPAN	4140H
SCM4H	JAPAN	4137
SCM4H	JAPAN	4137H
SCM4H	JAPAN	4140
SCM4H	JAPAN	4140H
SCM5	JAPAN	4147
SCM5	JAPAN	4147H
SCM5	JAPAN	4150

Information Handling Services, 2000

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
SCM5	JAPAN	4150H
SCM5H	JAPAN	4147
SCM5H	JAPAN	4147H
SCM5H	JAPAN	4150
SCM5H	JAPAN	4150H
SCMN2	JAPAN	1330
SCMN2	JAPAN	1330H
SCMN3	JAPAN	1335
SCMN3	JAPAN	1335H
SCMN3	JAPAN	1541
SCMN3	JAPAN	1541H
SCR2	JAPAN	5130H
SCR2H	JAPAN	5130H
SCR2H	JAPAN	5132
SCR3H	JAPAN	5132H
SCR3H	JAPAN	5135
SCR4H	JAPAN	5135H
SCR4H	JAPAN	5140
SCS19	JAPAN	304L
SKD1	JAPAN	D3
SKD12	JAPAN	A2
SKD5	JAPAN	H21
SKD6	JAPAN	H11
SKD61	JAPAN	H13
SKD62	JAPAN	H12
SKH2	JAPAN	T1
SKH3	JAPAN	T4
SKH4A	JAPAN	T5
SKH52	JAPAN	M3CLASS2
SKH53	JAPAN	M3CLASS2
SKN9	JAPAN	M2
SMN1H	JAPAN	1330
SMN1H	JAPAN	1330H
SMN2	JAPAN	1335
SMN2	JAPAN	1335H
SMN2	JAPAN	1541
SMN2	JAPAN	1541H
SMN2H	JAPAN	1335
SMN2H	JAPAN	1335H
SMN2H	JAPAN	1541
SMN2H	JAPAN	1541H
SMNC21	JAPAN	1022
SMNC21	JAPAN	1522H
SNCM21	JAPAN	8617
SNCM21	JAPAN	8617H
SNCM21	JAPAN	8620
SNCM21	JAPAN	8620H
SNCM21H	JAPAN	8617
SNCM21H	JAPAN	8617H
SNCM21H	JAPAN	8620
SNCM21H	JAPAN	8620H
SNCM8	JAPAN	4340
SNCM8	JAPAN	4340H
SUH309	JAPAN	316
SUH310	JAPAN	316L

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
SUH409	JAPAN	409
SUH616	JAPAN	422
SUM11	JAPAN	1110
SUM12	JAPAN	1110
SUM12	JAPAN	1212
SUM21	JAPAN	1212
SUM22	JAPAN	1213
SUM22L	JAPAN	12L14
SUM24L	JAPAN	12L14
SUP10	JAPAN	6150
SUP10	JAPAN	6150H
SUP11	JAPAN	50B50
SUP11	JAPAN	50B50H
SUP4	JAPAN	1095
SUS301	JAPAN	301
SUS303	JAPAN	303
SUS304	JAPAN	304
SUS304L	JAPAN	304L
SUS305	JAPAN	305
SUS305	JAPAN	308
SUS305J1	JAPAN	305
SUS305J1	JAPAN	308
SUS316	JAPAN	316
SUS316L	JAPAN	316L
SUS317	JAPAN	317
SUS321	JAPAN	321
SUS347	JAPAN	347
SUS403	JAPAN	403
SUS405	JAPAN	405
SUS410	JAPAN	410
SUS416	JAPAN	403
SUS420J1	JAPAN	420
SUS43	JAPAN	403
SUS430	JAPAN	430
SUS430F	JAPAN	430F
SUS431	JAPAN	431
SUS434	JAPAN	434
SUS440B	JAPAN	440B
SUS440C	JAPAN	440C
SUSY310	JAPAN	310
SUSY310	JAPAN	314
SUSY316	JAPAN	316
TYPE3	ENGLAND	5132H
TYPE3	ENGLAND	5135
TYPE7	ENGLAND	8640
TYPE7	ENGLAND	8640H
TYPE7	ENGLAND	8740
TYPE7	ENGLAND	8740H
TYPE8	ENGLAND	E4340
TYPE8	ENGLAND	E4340H
X105CRMO17	GERMANY	440C
X105CRMOI7	EURONORM	440C
X10CR13	ITALY	410
X10CRNIS1809	ITALY	303
X10CRNIS189	EURONORM	303

Information Handling Services, 2000

DATE: 12/23/88
STEEL

FOREIGN ALLOY CROSS REFERENCE
MSFC HANDBOOK 527F / JSC 09604F

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
X10CRNITI189	GERMANY	321
X10CRS17	ITALY	430
X10CRS17	ITALY	430F
X128W09KU	ITALY	H21
X12CR13	EURONORM	410
X12CR13	ITALY	403
X12CR13	ITALY	410
X12CR13KG	ITALY	410
X12CR13KW	ITALY	410
X12CRMOS17	GERMANY	430F
X12CRNI1707	ITALY	301
X12CRNI177	EURONORM	301
X12CRNI177	GERMANY	301
X12CRNIS188	GERMANY	303
X12CRS13	ITALY	416
X150CRMO12KU	ITALY	D2
X150WCOV130505KU	ITALY	T15
X15CR13	GERMANY	403
X16CRNI16	ITALY	431
X16CRNI2314	ITALY	309
X16CRNISI2520	ITALY	310
X16CRNISI2520	ITALY	314
X20CR13	EURONORM	420
X20CR13	GERMANY	420
X20CR13	ITALY	420
X20CR13X1	ITALY	420
X210CR13KU	ITALY	D3
X21CRNI17	EURONORM	431
X22CCRNI17	EURONORM	431
X22CRNI17	GERMANY	431
X22CRNI2520	ITALY	310
X22CRNI2520	ITALY	314
X2CCRNIMO1812	GERMANY	316L
X2CRNI1811	ITALY	304L
X2CRNI1811KG	ITALY	304L
X2CRNI1811KW	ITALY	304L
X2CRNI189	GERMANY	304L
X2CRNIMO1712	ITALY	316L
X2CRNIMO1713	ITALY	316L
X2CRNIMO1813	GERMANY	316LN
X2CRNIMO1816	GERMANY	317
X2CRNIMO1816	ITALY	317L
X2CRNIMON1812	GERMANY	316L
X2CRNIN1810	GERMANY	304LN
X35CRMO05KU	ITALY	H11
X35CRMOV05KU	ITALY	H13
X35CRMOW05KU	ITALY	H12
X3CCRNIMO17133	EURONORM	316L
X3CRNI1810	EURONORM	304L
X3CRNI1811	ITALY	403L
X3CRNIMO17122	EURONORM	316L
X3CRNIMO18164	EURONORM	317L
X40CR13	GERMANY	420
X5CCRNI1911	GERMANY	305
X5CRN9TI189	GERMANY	321

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
X5CRNI1810	ITALY	304
X5CRNI189	GERMANY	304
X5CRNIMO1712	ITALY	316
X5CRNIMO1713	ITALY	316
X5CRNIMO1810	GERMANY	316
X5CRNIMO1812	GERMANY	316
X5CRNIMO1815	ITALY	317
X5CRTI12	GERMANY	409
X6CCRM017	GERMANY	434
X6CCRNI1810	EURONORM	304
X6CCRNITI1810	EURONORM	321
X6CR13	EURONORM	410
X6CRAL13	EURONORM	405
X6CRAL13	ITALY	405
X6CRNI2314	ITALY	309S
X6CRNIMO17122	EURONORM	316
X6CRNIMO17133	EURONORM	316
X6CRNINB1810	EURONORM	347
X6CRNINB1811	ITALY	347
X6CRNITI1811	ITALY	321
X6CRNITI1811KG	ITALY	321
X6CRNITI1811KT	ITALY	321
X6CRNITI1811KW	ITALY	321
X75W18KU	ITALY	T1
X78WCO1805KU	ITALY	T4
X7CR13	GERMANY	410
X7CR17	EURONORM	430
X7CRAL13	GERMANY	405
X80WCO1810KU	ITALY	T5
X82MOW09KU	ITALY	M1
X82WMO0605KU	ITALY	M2
X8C417	ITALY	430
X8CCRMO17	ITALY	434
X8CR17	GERMANY	430
X8CR17	ITALY	430
X8CRMNNI189	GERMANY	202
X8CRMO17	EURONORM	434
X8CRMO17	ITALY	434
X8CRNI1812	EURONORM	305
X8CRNI1812	ITALY	305
X8CRNI1910	ITALY	305
X8CRNI1910	ITALY	308
X8CRNIMO257	GERMANY	329
X8CRNINB1811	ITALY	347
X8CRTI17	GERMANY	430TI
X90CRMOV18	GERMANY	440B
X90MOV18	GERMANY	440B
XC10	FRANCE	1010
XC15	FRANCE	1015
XC15	FRANCE	1017
XC18	FRANCE	1015
XC18	FRANCE	1017
XC18S	FRANCE	1023
XC25	FRANCE	1023
XC38TS	FRANCE	1038

Information Handling Services, 2000

FOREIGN ALLOY	ORIGINATING ORG	US EQUIVALENT
XC38TS	FRANCE	1038H
XC42	FRANCE	1042
XC42	FRANCE	1045
XC42	FRANCE	1045H
XC42TS	FRANCE	1042
XC42TS	FRANCE	1045
XC42TS	FRANCE	1045H
XC45	FRANCE	1042
XC45	FRANCE	1045
XC45	FRANCE	1045H
XC45TS	FRANCE	1049
XC48	FRANCE	1042
XC48	FRANCE	1045
XC48	FRANCE	1045H
XC48TS	FRANCE	1049
XC68	FRANCE	1070
XC75	FRANCE	1078
Z100C17	FRANCE	440C
Z100CD17	FRANCE	440C
Z100CDV5	FRANCE	A2
Z10C13	FRANCE	410
Z10CF17	FRANCE	430F
Z10CNF18.09	FRANCE	303
Z10CNF1809	FRANCE	303
Z110DKCWV0908040201	FRANCE	M42
Z110WKCDV0705040402	FRANCE	M41
Z120WDCV06050403	FRANCE	M3CLASS2
Z12C13	FRANCE	410
Z12CF13	FRANCE	416
Z12CN17.08	FRANCE	301
Z12CN1707	FRANCE	301
Z12CNS25.20	FRANCE	310
Z12CNS25.20	FRANCE	314
Z130WDCV06050404	FRANCE	M3CLASS2
Z15CDN160403	FRANCE	AM355
Z15CN16O2	FRANCE	431
Z15CN24.13	FRANCE	309S
Z200C12	FRANCE	D3
Z20C13	FRANCE	420
Z20CB	FRANCE	420
Z2CDN1712N	FRANCE	316LN
Z2CN1810	FRANCE	304L
Z2CN1810	FRANCE	404L
Z2CN1810N	FRANCE	304L
Z2CND17.12	FRANCE	316L
Z2CND1712	FRANCE	316L
Z2CND1713	FRANCE	316L
Z2CND1713N	FRANCE	316LN
Z2CND19.15	FRANCE	317L
Z2CND1915	FRANCE	317
Z30C130	FRANCE	420
Z30WCV9	FRANCE	H21
Z38CDV5	FRANCE	H11
Z40COV5	FRANCE	H13
Z6C13	FRANCE	410
Z6CA13	FRANCE	405
Z6CA13	FRANCE	409
Z6CN18.09	FRANCE	304
Z6CN1809	FRANCE	304
Z6CN1810	FRANCE	304
Z6CND17.11	FRANCE	316
Z6CND1711	FRANCE	316
Z6CND1712	FRANCE	316
Z6CNN618.10	FRANCE	347
Z6CNNB1810	FRANCE	347
Z6CNT18.10	FRANCE	321
Z6CNT1810	FRANCE	321
Z80WCV18-04-01	FRANCE	T1
Z80WCV180401	FRANCE	T1
Z80WKCV18-05-04-01	FRANCE	T4
Z80WKCV18050401	FRANCE	T4
Z85DCWV08-04-02-01	FRANCE	M1
Z85DCWV08040201	FRANCE	M1
Z85WDCV06-05-04-02	FRANCE	M2
Z85WDCV06050402	FRANCE	M2
Z8C17	FRANCE	430
Z8CD17.01	FRANCE	434
Z8CD1701	FRANCE	434
Z8CN1812	FRANCE	305
Z90WDCV06050402	FRANCE	M3CLASS1
ZZ10C14	FRANCE	410

Information Handling Services, 2000

MSFC-HDBK-527 REV F 9999942 0007209 4

TABLE 5

TEST MATERIAL QUANTITY REQUIREMENTS

Information Handling Services, 2000

TEST MATERIAL QUANTITY REQUIREMENTS (8060.1/8060.1A0

(All Requirements Based on one Test Atmosphere and Pressure)

Test Name & Number	Sheet Type (paper, Cloth, etc.)	Liquids, Lubes Heat Transfer Fluids, etc.	Coatings, Paintings, Inks, etc.	Foams	Insulated Electrical Wire	Potting & Molding Compounds
1. Upward Propagation	4 each, 6.4 X 30.5 cm (2-1/2" X 12") X "as received"	240 cc (1/2 pint)	Sufficient to cover 4 each, 6.4 X 30.5 cm (2-1/2" X 12") X required thickness	4 each, 6.4 X 30.5 cm (2-1/2" X 12") X required thickness	121 cm (48")	Sufficient to cover 4 each, 6.4 X 30.5 X o.3 cm (2-1/2" X 12" X 1/8") deep
2. Downward Propagation	4 each, 6.4 X 30.5 cm (2-1/2" X 12) X "as received" thickness	240 cc (1/2 pint)	Sufficient to cover 4 each, 6.4 X 30.5 cm (2-1/2" x 12") required thickness	4 each, 6.4 X 30.5 cm (2-1/2" X 12) X required thickness	121 cm (48")	Sufficient to cover 4 each, 6.4 X 30.5 X 0.3 cm (2-1/2" X 12" x 1/8") deep
3. Flash & Fire	(4 each, 1/2-gram samples or 1.25 cm (1/2" diameter by 1.25 cm (1/2" high cylinder)					
4. Electrical Wire Flammability	N/A	N/A	N/A	N/A	Minimum of 305 cm (120") of wire per run. 914 cm (360") total for 3 runs.	N/A
5. Electrical Connector Flammability	N/A	N/A	N/A	N/A	N/A	At least 480 cc (=1.0 pint) of material when cured.
6. Odor ⚠1	2000 cm^2 (310 $IN.^2$) (both sides)	40 grams (1.41 oz.)	2000 cm^2 (310 $In.^2$ (both sides) Or 1.0 pint	500 cm^2 (Surface) (77.5 $In.^2$)	40 grams (1.41 oz.)	40 grams (1.41 oz.)
7. CO/TO ⚠1 ⚠2	2000 cm^2 (310 $In.^2$) (both sides)	40 grams (1.41 oz.)	2000 cm^2 (310 $In.^2$) (both sides) or 1.0 pint	500 cm^2 (Surface) (77.5 $In.^2$)	40 grams (1.41 oz.)	40 grams (1.41 oz.)
8. Unused						
9. Unused						

TEST MATERIAL QUANTITY REQUIREMENTS (8060.1/8060.1A0

(All Requirements Based on one Test Atmosphere and Pressure)

Test Name & Number	Sheet Type (paper, Cloth, etc.)	Liquids, Lubes Heat Transfer Fluids, etc.	Coatings, Paintings, Inks, etc.	Foams	Insulated Electrical Wire	Potting & Molding Compounds
13. GOX Impact & (Mech. & 14. Pneu.)	NHB8060.1 LOX/GOX-Mech. 240 Specimens 1.75 cm (11/16") dia. Max. thick- - .35 cm (1/8")	120 cc (4 oz.)	120 cc (4 oz.)	NHB8060.1 LOX/GOX-Mech. 240 Specimens 1.75 cm (11/16") dia. Max. thick- -.35 cm (1/8")	30.5 cm (12")	120 cc (4 oz.)
	GOX Pneumatic 80 Samples .475 cm (3/16") dia. Max. thickness - .35 cm (1/8")			GOX Pneumatic 80 Samples .475 cm (3/16") dia. Max. thickness - .35 cm (1/8")		
	Quantities listed are for testing at one pressure.			Quantities listed are for testing at one pressure.		
15. Category J Fluids Constant Temperature Immersion Test ⚠3	4 each 5.1 cm X .64 cm X .64 cm (2" X 1/4" X 1/4") 4 each total surface area = 13.6 cm^2 (2.1 $in.^2$)	280 gm (10 oz.)	480 cc = (1.0 pint)	4 each 5.1 cm X .64 cm X .64 cm (2" X 1/4" X 1/4") or 4 each total surface area = 13.6 cm^2 (2.1 $in.^2$)	305 cm (120")	4 each 5.1 cm X .64 cm X .64 cm (2" X 1/4" X 1/4") or 4 each total surface area = 13.6 cm^2 (2.1 $in.^2$)
VCM SP-R-0022	20.0 Grams .704 Ozs.	20.0 Grams .704 Ozs.	20.0 Grams .704 Ozs.	20.0 Grams .704 Ozs.	20.0 Grams .704 Ozs.	20.0 Grams .704 Ozs.
TGA JSC-PA-D-67-13	20.0 Grams .704 Ozs.	20.0 Grams .704 Ozs.	20.0 Grams .704 Ozs.	20.0 Grams .704 Ozs.	20.0 Grams .704 Ozs.	20.0 Grams .704 Ozs.

⚠1 Amounts and quantities given are for a 4 liter container for odor and for a 4-liter container for CO/TO.

⚠2 Due to WSTF safety criteria, a CO/TO test must be performed before any odor test can be performed, except in special cases where only one item is available for testing. Therefore, enough material must be submitted for both CO odor Tests in order to perform any Odor Test.

⚠3 Quantities include enough materials to conduct WSTF screening test.

GOVERNMENT PRINTING OFFICE: 1988 -631-056/ 24